MORPHOLOGICAL ASPECTS OF SURFACE REACTIONS

Progress Report

September 1991 - August 1992

J. M. White

Department of Chemistry

University of Texas

Austin, Texas 78712

August 1992

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PREPARED FOR THE U.S. DEPARTMENT OF ENERGY

UNDER GRANT NUMBER DE-FG05-86ER13626

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

1. Project Title: Morphological Aspects of Surface Reactions

John M. White, Principal Investigator
The University of Texas at Austin
Department of Chemistry
Austin, Texas 78712
(512)471-3704
FAX: 471-9495

2. Principal Project Personnel

John M. White

A. Role in the project: Principal Investigator

B. Principal areas of research and expertise: surface chemistry,
the dynamics of surface reactions, photoassisted surface
reactions

C. An indication of the percentage of time devoted to the project:
(15)

D. Education: B.S. in chemistry, Harding College, 1960
Ph.D. in chemistry, University of Illinois, 1966

E. Relevant employment history: The University of Texas at Austin,
Assistant Professor, 1966-1970; Associate Professor, 1970-76;
Professor, 1976-present; Norman Hackerman Professor of
Chemistry, 1985-present. National Science Foundation, Program
Officer, 1978-79. Summer guest worker, National Bureau of
Standards, 1978-79.

Also, since 1991: Director, The University of Texas Science
and Technology Center for the Synthesis, Growth, and Analysis
of Electronic Materials.

F. Relevant professional activities and honors: Currently, member
of ACS, AVS, MRS; Editorial Board, CRC Critical Reviews in
Chemistry; Chemical and Laser Sciences Advisory Committee, Los
Alamos National Laboratory. Honors include Outstanding
Alumnus Award, Harding University, 1991; ACS Kendall Award,
1990; Humboldt Senior Scientist Award, 1989; Outstanding
Alumnus Award, Alpha Chi, 1986.

3. Additional Project Personnel

Members of Technical Staff

All of the following are or have been active participants in research and have contributed significantly to publications arising from the work performed under this grant.

Diann Alberas, Ph.D. student in chemistry, UT-Austin

Alex Boffa, undergraduate student in chemistry, UT-Austin

Deborah Buchanan, Ph.D. student in chemistry, UT-Austin

Maria Curelaru, Ph.D. student in chemistry, UT-Austin

Cynthia Flores, postdoctoral fellow; Ph.D. (chemistry) from
University of California, Irvine

Aaron Golchet, technical staff assistant; Ph.D. (chemistry) from
UT-Austin

Bryon Hance, Ph.D. student in chemistry, UT-Austin

Helen Hernandez, visiting graduate student from the University of
Texas at El Paso

Tom Huett, Ph.D. student in chemistry, UT-Austin

Ze-ming Liu, Ph.D. student in chemistry, UT-Austin

Laura Pressley, Ph.D. student in chemistry, UT-Austin

Derrell Sloan, Ph.D. student in chemistry, UT-Austin

Xioayang Zhu, Research Scientist Associate, UT-Austin

Collaborators

Professor Frigyes Solymosi, Full Professor and Head of the Reaction Kinetics Research group at the Hungarian Academy of Sciences; also Head of the Institute for Solid State and Radiochemistry at the Attila Jozsef University. Ph.D. in chemistry from the University of Szeged, D.Sc. from the Hungarian Academy of Sciences. Principal areas of expertise: heterogeneous catalysis, surface science, solid state chemistry.

4. Project Overview

This program involves the preparation and characterization, both structural and kinetic, of a variety of metal-based catalysts and adsorbates thereon. Both model and technically attractive adsorbate-substrate systems are being investigated using the tools of catalytic and surface chemical science. The substrates involve mainly rhodium and silver as well as combinations of the two. Single crystal, thin film, oxide-bound molecular metal species and oxide-supported particles are included in an integrated program. Oxides of silicon, aluminum and titanium are being used for supports for particles and thin metal films. The morphology and electronic structure of the metals are being characterized by tunneling microscopy and tunneling spectroscopy. Adsorbates include carbon oxides, halogenated hydrocarbons, benzene and alkalis. Particular attention is being given to the synthesis of hydrocarbon fragments, for example, methyl, ethyl and propyl, by photochemical and electron-induced methods, at temperatures low enough to accumulate and preserve the fragments for subsequent structural, kinetic, and reactivity characterization. The short-range goal of this research is to develop detailed structural and kinetic parameters for well-characterized adsorbate-substrate systems by controlling and elucidating the substrate preparation chemistry, the adsorbate-substrate chemistry and the product evolution chemistry. Throughout, even-handed attention is given to both structure and kinetics. The long-range goal of the research is to develop relevant kinetic and structural parameters for technically important systems based on model laboratory catalytic systems.

Our research group has, for several years, given particular attention to the kinetics of surface species. To make kinetic measurements on surface intermediates naturally involves their structural characterization. Thus, structure and kinetics are integrated systematically in our program. It is our view that understanding the kinetics of structurally well-characterized laboratory model systems is crucial to making connections between these models and technical catalysts. Furthermore, it is important to build some models that represent as closely as possible actual technical materials. Thus, this research program involves thin metal films and metal particles on oxide supports, as well as single crystal metals.

The following kinds of systems are being examined: (1) supported molecular metal complexes, (2) supported metal particles, (3) thin metal films on oxide and metal supports, and (4) unsupported metal single crystals. The metals of central interest are Ag and Rh, including bimetallic Ag/Rh. The adsorbates of interest are hydrocarbons and surface-bound hydrocarbon fragments prepared by thermal, photo, and electron-induced methods.

Photochemistry. We are using photochemistry as a tool to prepare a variety of alkyl fragments on Ag(111) and Ag(110). Once these fragments are prepared and characterized by HREELS, XPS, TPD, $\Delta\Phi$ and static SIMS measurements, the kinetics of their decomposition can be traced in real time using static SIMS and TPD and in an intermittent fashion with HREELS and XPS. Based on our success with Pt(111), we anticipate successful photochemical preparation at 100 K of these same fragments on Rh. Compared to Ag, we expect the thermal chemistry to be very different, as Rh should catalyze both C-C and C-H bond breaking. Assuming for now that this is the case, then the alteration, by submonolayers of added Ag, of the reactivity of hydrocarbon fragments on Rh will be of great kinetic interest. For example, just how much Ag does it take to passivate the Rh substrate for C-C and C-H bond cleavage in alkyl fragments?

Electron-driven chemistry. In parallel with the photochemistry described above, we are pursuing electron-stimulated decomposition of adsorbates at surfaces. While the general underlying ideas are the same -- electronic excitation followed by bond rearrangement -- the details differ in interesting ways.

The combination and comparison of photochemistry with electron-induced chemistry offers a unique opportunity to prepare and characterize, kinetically and structurally, a number of surface fragments. Benzene is of interest because it has a complex gas phase optical absorption spectrum in the 200 - 300 nm region and has highly studied photochemistry and photophysics, including fluorescence and singlet-triplet crossover properties. Unlike the alkyl halides, in gas phase benzene, bond cleavage occurs with only a very small quantum yield. Thus, we wish to explore the possibility of metal-catalyzed photodissociation or rearrangement of benzene on Ag(111).

Tunneling microscopy. Using tunneling methods, we are studying the morphology and electronic structure, on model oxide supports, of Rh particles. We have designed, constructed and successfully operated, for atomic scale imaging of pyrolytic graphite surfaces and for current-voltage curves giving occupied and unoccupied density of states, a novel UHV STM that fits into a conventional surface analysis chamber with capabilities for AES, thermal processing, TPD, metal dosing, and LEED. The sample is mounted so that it moves on a 2" circle within the UHV chamber to access these capabilities. The STM tip does not travel with the sample. Through a combination of mechanical and piezo-electric motions, the sample can be returned to the tunneling position (obviously not to the same lateral location atomically) from any of the other measurement/treatment positions. Thermal drift after heating requires multi-hour waiting, so rapid time-dependent analysis is not possible. It is feasible to anneal, quench, wait for

thermal drift to reach tolerable limits, and then do tunneling measurements. Assuming quenched Rh species are stable for several hours around room temperature, all the measurements become technically feasible.

Overall Program. This program is concerned with the role played by particle size, shape and surface atom arrangement in determining the catalytic activity of metal catalysts. This remains an outstanding scientific problem and one which, we believe, will yield only to an integrated effort that involves a molecular level surface science approach to the chemistry involved in the preparation of both the substrate and the adsorbate. Because of the central role of metal-based heterogeneous catalysts in hydrocarbon- and coal-based technologies, this kind of work has, at the fundamental science level, important contributions to make to the knowledge base on which these technologies depend.

6. Project Output

In this section, we provide considerable detail regarding the progress of our DOE-supported work over the previous three-year funding period.

6.1. Substrate structural studies.

STM on TiO₂(001). There has been great interest in the surfaces of TiO₂, e.g., their photocatalytic activity in the oxidation of water and organic compounds.¹⁻⁴ Numerous surface science techniques have been applied to gain a better understanding of the structure of these surfaces.⁵⁻¹⁴ The studies described here combined low energy electron diffraction (LEED) and Auger electron spectroscopy (AES) with scanning tunneling microscopy (STM) to determine the *local* structure of thermally faceted TiO₂(001) rutile.

In 1977, Somorjai et al. first reported that the (001) face of TiO₂(001) is unstable and facets on annealing.¹¹ These conclusions were based on LEED, AES, and electron energy loss spectroscopy (EELS). In 1979, Tait and Kasowski studied this surface using ultraviolet photoelectron spectroscopy (UPS), LEED and *ab-initio* calculations.^{5,6} Based on dynamical LEED measurements, they proposed that at temperatures above 475 °C it facets to {111} or {011}; they defined this as phase I. At temperatures above 950 °C, they concluded that the (001) face reconstructs to give LEED patterns with symmetry $n/\sqrt{2} \times 1[R(45^\circ)]$ ($n=4, 5$ or 8); this they defined as phase II. In 1982, by comparing experimental and calculated LEED images over a range of energies, Firment concluded that the phase I surface consists of (011) facets and the phase II surface of (114).⁸ The transformation from phase I to phase II is gradual, with domains of both structures existing

at intermediate temperatures.

Bulk, stoichiometric TiO_2 rutile has 6-coordinate titanium and 3-coordinate oxygen. Simple bulk termination in the (001) plane results in 4-coordinate titanium and 2-coordinate oxygen; the high free energy associated with this high degree of coordinative unsaturation is the driving force for faceting.

We have studied a low temperature (Phase I) thermally faceted $\text{TiO}_2(001)$ rutile surface using STM, AES and LEED. (001) planes on the order of 20 Å wide and {011}, {023}, {045}, {114} and {111} facet planes on the order of 200 Å wide were observed. Straight step edges running in low index directions were seen on the facet planes. The observed step structure on (011) planes and the structure of (114) facets suggested facet growth by surface migration. Our STM and LEED data are in good agreement with previous LEED and ESDIAD data; however, the STM images provided local detail not possible from spatially averaging techniques.

A major advantage of this STM study, compared to LEED, is that it gives a *distribution* of facet planes; from this we can draw some conclusions about their relative surface free energies (g). A detailed discussion of the theory of thermal faceting (also called thermal etching) is beyond the scope of this report, but can be found in several review articles and monographs.¹⁵⁻¹⁸ Briefly, Wulff's theorem¹⁶ states that a solid's equilibrium shape will exhibit extended planes (facets) only for faces for which the corresponding direction on a polar plot of g has an inward pointing cusp. The width of a facet plane will depend on the "pointedness" of the cusp and on the behavior of $g(q,f)$ in the neighborhood of the facet.^{18,19} Though our crystal is not in its equilibrium geometry (it would be more spherical if it was) our data is indicative of cusps in $\langle 011 \rangle$, $\langle 023 \rangle$, $\langle 045 \rangle$, $\langle 114 \rangle$ and $\langle 111 \rangle$ directions of $g(q,f)$. From a more extensive analysis of the width and preponderance of various facets, it may be possible to determine their relative g 's. We leave this for a future exercise.

References

- [1] S. Sato and J. M. White, Chem. Phys. Lett. **72**, 83 (1980).
- [2] A. J. Bard, J. Photochem. **10**, 59 (1979).
- [3] A. H. Boonstra and C. Mutsaers, J. Phys. Chem. **79**, 2025 (1975).
- [4] Y. Onishi and T. Hamamura, Bull. of Chem. Soc. Japan, **43**, 996 (1970).
- [5] R. H. Tait and R. V. Kasowski, Phys. Rev. B **20**, 5178 (1979).
- [6] R. V. Kasowski and R. H. Tait, Phys. Rev. B **20**, 5168 (1979).
- [7] R. L. Kurtz, Surface Sci. **177**, 526 (1986).
- [8] L. E. Firment, Surface Sci. **116**, 205 (1982).
- [9] S. E. Gilbert and J. H. Kennedy, Surface Sci. Lett. **225**, L1 (1984).
- [10] S. Munnix and M. Schmeits, Phys. Rev. B **30**, 2202 (1984).
- [11] Y. W. Chung, W. J. Lo and G. A. Somorjai, Surface Sci. **64**, 588 (1977).
- [12] V. E. Henrich, Rep. Prog. Phys. **48**, 1481 (1985).

- [13] G. D. Davis, M. Natan and K. A. Anderson, *Appl. of Surface Sci.* **15**, 321 (1983).
- [14] J. Wonig and R. A. Van Santen, *Chem. Phys. Lett.* **101**, 541 (1983).
- [15] Metal Surfaces: Structure, Energetics and Kinetics, Ed. American Society of Metals, (1963). The most relevant chapters are: 1 by F. C. Frank, 4 by N. A. Gjostein, and 5 by A. J. W. Moore.
- [16] G. Wulff, *Z. Kristallogr.* **34**, 449 (1901).
- [17] C. Herring, *Phys. Rev.* **82**, 87 (1951), and references therein.
- [18] M. Drechsler and J. F. Nicholas J. *Phys. Chem. Solids* **28**, 2609 (1967), and references therein.
- [19] R. Defay and I. Prigogine, Surface Tension and Adsorption, p. 286, Longmans, Green Co. (1966).

6.2. Fragments synthesized by thermal activation.

Hydrocarbon fragments -- thermal processes. We have surveyed a series of alkyl iodides on Ag(111) using temperature programmed desorption (TPD). These include C_2H_3I , $n-C_3H_7I$, $i-C_3H_7I$, $ClCH_2I$, and $Cl(CH_2)_3I$. All of these dissociate thermally during TPD after adsorption at 100 K. Typical of Ag, the resulting hydrocarbon fragments recombine, without further C-H or C-C bond breaking, and desorb as higher hydrocarbons by forming C-C bonds, i.e., butadiene from C_2H_3 etc. It is interesting that the C-Cl bond in $ClCH_2I$ is broken, since C-Cl bonds in CH_3Cl do not break. We take this as evidence that once the C-I bond is broken in $ClCH_2I$, the C-Cl bond in $ClCH_2$ will break because this fragment is much more tightly held to the Ag and because the C-Cl bond is weakened.

Thermal chemistry of C_2H_3I . In a companion study on Pt(111), we have examined the thermal chemistry of C_2H_3I . Regardless of exposure, only submonolayer amounts decompose; the remainder desorbs molecularly. The dissociation product is vinyl, an important C_2 intermediate in hydrocarbon catalysis and atomic iodine. Consistent with our program goal of synthesizing and characterizing hydrocarbon intermediates on metal surfaces, we have used the tools of surface science to examine vinyl, in this case in the unavoidable presence of coadsorbed atomic I. While some vinyl exists up to 450 K, there are two important and competitive lower temperature reaction channels; they lead to ethynyl (CCH_3) and ethylene (C_2H_4). *Based on transient kinetic data (TPD and static secondary ion mass spectrometry, SSIMS) and vibrational data (high resolution electron energy loss spectroscopy, HREELS) for vinyl, we conclude that the conversion rate of ethylene to ethynyl on Pt(111) is controlled by the rate at which the first C-H bond breaks (i.e., the conversion of vinyl to ethynyl is much faster and does not control the rate). It is just this kind of detailed understanding that is the goal of our program.*

POTD -- vinyl to ethylidyne. Because of the facile nature of the conversion of vinyl to ethylidyne on Pt(111), it is a challenge to characterize quantitatively the kinetics. In the process of pursuing this issue, we have developed a new tool for diagnosing surface reactions that involve C-H bond cleavage -- predosed oxygen TPD (POTPD). To review, it is well known [2] that C_2H_4 , chemisorbed on Pt(111) at low temperatures, is di- σ bonded and converts to ethylidyne (CCH_3) around 300 K with simultaneous desorption (in the form of H_2) of one fourth of the total hydrogen. $CCH_3(a)$ decomposes above 450 K to form gaseous H_2 and surface carbon. The mechanism by which di- σ $C_2H_4(a)$ converts to $CCH_3(a)$ remains controversial. Using static secondary ion mass spectrometry (SSIMS), we find that vinyl starts to convert to $CCH_3(a)$ near 130 K, i.e., a low activation barrier. Comparing the behavior of C_2H_3I and C_2H_4 on Pt(111), we suggested [1] that $CHCH_2$ is an important intermediate and that the rate is controlled by breaking the first C-H bond in di- σ bonded $C_2H_4(a)$. However, the pathway from $CHCH_2(a)$ to $CCH_3(a)$ remains to be established. Is this conversion an intramolecular 1,2-hydrogen shift reaction, which does not require the Pt substrate atoms, or do the Pt atoms participate strongly in the transition state?

We have developed pre-dosed oxygen temperature programmed desorption (POTPD) to examine this question in more detail. POTPD is a thermal desorption and reaction technique based on scavenging surface H(a) by small amounts of preadsorbed O(a) to form water [3]. This water desorbs at very low temperatures and is easily detected mass spectrometrically. More importantly, when hydrocarbon fragments supply H(a), this water monitors C-H bond cleavage and, thus, characterizes the kinetics of dehydrogenation of hydrocarbon fragments on Pt(111). While a detailed description of this technique will be published [4], we provide an outline here. A very low coverage (<0.02 ML) of atomic oxygen, O(a), is first prepared on a clean Pt(111) surface and then the hydrogen-containing molecules are adsorbed at low temperatures (~ 100 K). The O(a) coverage is kept very low so there is negligible perturbation of the dehydrogenation process. During heating, provided background H(a) is accounted for, O(a) remains until C-H bonds break. The resulting H(a) reacts promptly with O(a) to form H_2O that desorbs. Thus, the H_2O TPD reflects the dehydrogenation process.

Consider the conversion of $CHCH_2(a)$ to $CCH_3(a)$ on Pt(111). If the pathway involves an intramolecular 1,2-hydrogen shift, then no H_2O will be formed during this process, since no H atoms are bonded to Pt, even transiently. If, however, a transient H-Pt bond is involved, then H_2O will be formed. Our results indicate that transient Pt-H bonds are formed beginning about 130 K, consistent with earlier TPSSIMS results [1].

We also find evidence that the conversion of $\text{CHCH}_2(\text{a})$ to $\text{CCH}_3(\text{a})$ on $\text{Pt}(111)$ is not a simple H atom shift; rather, it involves a transient Pt-H bond. We propose an intermediate in which the shifting H atom is partially bonded to two C atoms and one Pt atom. The POTPD spectra are adequately fit with an activation energy and pre-exponential factor for the $\text{CHCH}_2(\text{a})$ to $\text{CCH}_3(\text{a})$ conversion of 2.4 ± 0.2 kcal/mol and $10^{1.4 \pm 0.2} \text{ s}^{-1}$, respectively. This is a step in the right direction insofar as our goals are concerned -- synthesis and characterization of catalytically interesting hydrocarbon fragments.

References:

- [1] Z.-M. Liu, X.-L. Zhou, D. A. Buchanan, J. Kiss and J. M. White, *J. Am. Chem. Soc.* 114 (1992) 2031.
 - [2] E. A. Carter and B. E. Koel, *Surface Sci.* 226 (1990) 339, and references therein.
 - [3] K. M. Ogle and J. M. White, *Surface Sci.* 139 (1984) 43.
 - [4] X.-L. Zhou and J. M. White, to be published.
-

Role of potassium. In a very interesting study, we have shown that CO, which does not adsorb on Ag at 100 K, cannot be induced to adsorb in the presence of K, at least for potassium coverages below 1 monolayer (ML) and CO doses less than 10^4 Langmuir (L). Thus, in spite of the known ability of K to alter dramatically the bonding of CO on transition metals, these results make it clear that the strength of bonding to the K-free substrate metal is also an important consideration.

In a series of studies involving collaboration with Solymosi's group in Szeged, Hungary, we have examined the detailed surface science of K on $\text{Ag}(111)$, the reaction of water with $\text{K}/\text{Ag}(111)$, and the formation of carbonate in $\text{CO}_2/\text{H}_2\text{O}/\text{K}/\text{Ag}(111)$ systems. The results, which qualitatively follow expectations based on other K-metal systems and inorganic chemistries, provide a detailed set of well-characterized systems, e.g., $\text{KOH}/\text{Ag}(111)$ and $\text{CO}_3^-/\text{K}/\text{Ag}(111)$, for use as substrates in future work.

The decomposition of CH_3Br on $\text{Ag}(111)$, promoted by potassium, has been examined. In contrast to the K-free surface, on which CH_3Br adsorbed and desorbed with no detectable decomposition, there is considerable decomposition when K is added. Carbon-bromine bond cleavage proceeds readily, even at 100 K, most of the CH_3 fragments desorb promptly and there is no measurable temperature dependence between 100 and 300 K. The dissociation is attributed to electron harpooning, i.e., the low work function of the K-covered surface and the electron affinity of the CH_3Br make it easy to inject an electron into CH_3Br . After harpooning, the CH_3Br^- is in a state that is repulsive with respect to the C-Br bond and dissociation follows. The absence of an activation energy is easy to understand -- electron harpooning is a tunneling process, which has negligible temperature dependence.

Nitrogen-containing compounds. The adsorption and decomposition of hydrazine has been studied on several metal surfaces [1-14]. According to these reports, decomposition can occur by a number of different paths, depending on the metal. In one path, the N-N bond breaks first, leaving NH_2 species on the surface. These typically decompose to N and H, which, upon thermal activation, recombine to desorb N_2 and H_2 . In a second path, the NH_2 species react with H to desorb NH_3 . In a third path, the N-H bonds break first, forming species such as N_2H_3 , N_2H_2 , N_2H , and N_2 . In this case, N_2 is formed intramolecularly, not by N atom recombination. In a fourth path, hydrazine is directly hydrogenated in a concerted reaction to form ammonia.

Different combinations of these paths have been invoked on different surfaces. For example, on Fe(111) [4] and Al foil [6], only the first path is reported. On Rh(111) [13], all the paths are reported depending on the concentration (coverage) of surface fragments. For example, on Rh foil [14], at low coverages, the first path is reported, whereas at high coverages, all paths are reported.

We have studied the thermal decomposition of hydrazine, N_2H_4 , adsorbed on a Pt(111) surface at 60 K by temperature programmed desorption (TPD), high resolution electron energy loss spectroscopy (HREELS), X-ray photoelectron spectroscopy (XPS), ultraviolet photoelectron spectroscopy (UPS), and temperature programmed secondary ion mass spectroscopy (TPSIMS). Condensed multilayer and chemisorbed states of hydrazine can be distinguished. Submonolayer hydrazine coverages start to decompose between 150 and 200 K by dissociation of N-H, not N-N, bonds. In TPD, H_2 , NH_3 , and N_2 all peak near 310 K. N_2 and NH_3 desorb in processes limited by the rates of the reactions forming them. N_2 is formed by an *intramolecular* process. No nitrogen containing species are detected above 400 K in HREELS or XPS. Depending on the surface coverage and temperature, dihydrogen desorption is probably limited by both the recombination rate and the rate of N-H cleavage. We propose that: (1) the low temperature N-H bond cleavage and the retention of N-N bonds, are facilitated by the chemisorption of N_2H_4 through both nitrogen atoms, and (2) relative to the N-metal bond, the H-metal bond is stronger on Pt(111). As a result, the barrier to N-H cleavage is lowered much more than the barrier to N-N cleavage, and the former is preferred.

References:

- [1] J. P. Contour and G. Pannetier, J. Catalysis 24 (1972) 434.
- [2] B. J. Wood and H. Wise, J. Catalysis 39 (1975) 471.
- [3] M. H. Matloob and M. W. Roberts, J. Chem. Research S (1977) 336.
- [4] M. Grunze, Surf. Sci. 81 (1979) 603.
- [5] H. H. Sawin and R. P. Merrill, J. Chem. Phys. 73 (1980) 996.
- [6] D. W. Johnson and M. W. Roberts, J Electron Spectroscopy and Related Phenomena 19 (1980) 185.

- [7] M. Kiskinova and D. W. Goodman, Surf. Sci. Lett. 109 (1981) L555.
- [8] J. L. Gland, G. B. Fisher and G. E. Mitchell, Chem Phys Lett. 119 (1985) 89.
- [9] W. M. Daniel and J. M. White, Surf. Sci. 171 (1986) 289.
- [10] D. M. Littrell and B. J. Tatarchuk, J. Vacuum Sci. Technol. A4 (1986) 1608.
- [11] D. M. Littrell, D. H. Bowers and B. J. Tatarchuk, J. Chem. Soc., Faraday Trans. I. 83 (1987) 3271.
- [12] G. A. Papapolymerou and L. D. Schmidt, Langmuir 3 (1987) 1098.
- [13] M. L. Wagner and L. D. Schmidt, Surf. Sci. 257 (1991) 113.
- [14] J. Prasad and J. L. Gland, Langmuir 7 (1991) 722.

6.3. Fragments synthesized by electron activation.

Synthesis of phenyl groups on Ag(111). The study of interactions of photons and electrons with adsorbate-substrate systems is an important area in surface chemistry and physics, which has many implications in basic science and technology. Electron stimulated desorption (ESD) is a well-established phenomenon [1]. Surface photochemistry on metals is relatively new, but has been developing rapidly in recent years [2]. When an adsorbate-metal system is exposed to either photons or electrons, several processes occur. These include decomposition of the adsorbate, desorption of the parent adsorbate and desorption of fragments. In some cases, the decomposition products are the same for both photons and electrons [3,4]. While studies of photon and electron stimulated desorptions of surface species are important to the understanding of the dynamics of these processes, studies focusing on the fragments retained at the surface are also helpful, particularly for the kinetics. Photon and electron induced decompositions of adsorbates are also effective ways to synthesize interesting fragments for fundamental catalytic studies [5,6].

We have studied the interaction of UV photons and low energy electrons with chemisorbed benzene (C_6D_6) on Ag(111) using temperature programmed desorption (TPD) and ultraviolet photoelectron spectroscopy (UPS). The surface chemistry of benzene on transition metal surfaces has been extensively studied in the past [7]. In particular, on Ag(111) it has been studied by vibrational and electronic EELS [8], angle-resolved UPS and LEED [9], NEXAFS [9] and Raman spectroscopy [9]. Benzene was found to lie flat (π -bonded) with C_{3v} (σ_d) symmetry and to form a (3x3) structure at monolayer coverage [9]. We find that C_6D_6 molecules adsorb weakly on Ag(111) at 100 K and desorb molecularly at ~160 K (physisorbed) and 208-220 K (chemisorbed) with no decomposition. The adsorption lowers the work function of Ag(111) by 0.7 eV at monolayer and 0.9 eV at multilayer coverages. *No photoeffects* are observed when

chemisorbed $C_6D_6(a)$ is exposed to UV photons generated from a high pressure Hg arc lamp. But *exposure to electrons results in selective decomposition* of $C_6D_6(a)$ to surface D atoms and phenyl fragments. The cross section for electron induced decomposition of $C_6D_6(a)$ at one monolayer coverage is $(1.9 \pm 0.1) \times 10^{-17} \text{ cm}^2$ at 50 eV. It decreases with decreasing incident electron energy and has a threshold between 11 and 16 eV. Surface D atoms desorb as D_2 at $\sim 200 \text{ K}$. Phenyl fragments recombine and desorb as biphenyl at 375-390 K; they do not decompose. Thus, low energy electron induced decomposition of C_6D_6 on Ag(111) is an effective way to prepare surface phenyl fragments.

References:

- [1] R. H. Stulen, Progress in Surf. Sci. 32 (1989) 1.
 - [2] J. M. White, Proc. 9th Intern. Summer Institute in Surf. Sci. (Milwaukee, WI, 1989).
 - [3] X.-L. Zhou and J. M. White, J. Chem. Phys. 92 (1990) 5612.
 - [4] X.-L. Zhou, S. R. Coon and J. M. White, J. Chem. Phys. 92 (1990) 1498. X.-L. Zhou and J. M. White, J. Phys. Chem. 94 (1990) 2643.
 - [5] K. G. Lloyd, B. Roop, A. Campion, and J. M. White, Surf. Sci. 214 (1989) 227. K. G. Lloyd, A. Campion, and J. M. White, Catal. Lett. 2 (1989) 105.
 - [6] X.-L. Zhou, P. M. Blass, J. M. White and B. E. Koel, (to be published).
 - [7] H.-P. Steinruck, W. Huber, T. Pache and D. Menzel, Surf. Sci. 218 (1989) 293, and references therein.
 - [8] Ph. Avouris and J. E. Demuth, J. Chem. Phys. 75 (1981) 4783.
 - [9] R. Dudde, K.-H. Frank and E. E. Koch, Surf. Sci. 225 (1990) 267.
-

Electron-induced decomposition of ethylene. As a part of our continuing investigation of photon [1] and electron [2-4] driven processes at adsorbate-metal interfaces, we report on the chemistry, induced by 50 eV electrons, of ethylene adsorbed on clean, Cl-, and D-covered Ag(111) at 100 K. While intrinsically interesting, nonthermal means of activating adsorbed species also offer opportunities to prepare and study intermediates, thought to be catalytically important. For example, heterogeneous hydrocarbon catalysis is a complex multiphase kinetics problem; many intuitively attractive surface intermediates have been proposed, but few of these hydrocarbon fragments have been cleanly synthesized and characterized structurally and kinetically. One elegant approach to adsorbed CH_3 fragments involves the dissociation of CH_4 during energetic collisions with Ni(111) [5], but generalizing this to species containing more than one carbon atom appears difficult. A second approach, of greater generality but less attractive because a coadsorbate is unavoidable, is the thermal dissociation of alkyl iodides [6], including vinyl iodide [7]. A third approach involves the photodissociation of alkyl halides [8]. A fourth approach, and one we have used, relies on controlled fluxes of low energy electrons to drive bond-specific non-thermal adsorbate chemistry.

In the absence of electron irradiation, C_2H_4 is weakly π -bonded and desorbs, with no thermal decomposition, below 170 K. Consistent with π -donation and π -polarization, one monolayer of ethylene lowers the work function by 0.38 eV. For low electron (50 eV) exposures ($< 1 \times 10^{15} e^-$), 1,3-butadiene (above 240 K) and H_2 (between 150 and 240 K) are the only desorbing products. They are attributed to vinyl (C_2H_3) fragments and H atoms formed by selective electron-driven C-H bond cleavage. Ionization of the adsorbate probably provides the activation. Above $1 \times 10^{15} e^-$, other TPD species are found and ascribed as follows: some C_2H_3 decomposes to acetylene, which desorbs at ~ 155 K; electron-induced recombination of some C_2H_3 forms C_4H_6 , which desorbs at ~ 195 K; and part of the π -bonded C_2H_4 is converted to di- σ bonded C_2H_4 . Butene (C_4H_8) is also observed and attributed to thermally activated fragment association reactions during TPD, e.g., C_2H_5 and C_2H_3 , and $-CH_2CH_2-C_2H_3$ and H. In the presence of Cl, the parent ethylene is stabilized and the amount of C_4H_6 produced in TPD is enhanced. For ethylene and coadsorbed D, there is, in the absence of electron irradiation, no reaction. With electron irradiation, isotopically labelled dihydrogen and partially deuterated ethylene and ethane form, but there are no C_1 , C_3 or C_4 products. We propose that bond-specific decomposition, e.g., C-H bond cleavage to form vinyl, occurs when the weakly bound ethylene is ionized by low energy electrons. That further C-H bond cleavage occurs with much lower cross-section and that there is no C-C bond cleavage may result from relatively effective quenching of excited ionic states of the strongly chemisorbed primary product, C_2H_3 .

Ag is an important and interesting catalytic metal. For example, the reaction of ethylene and oxygen to form ethylene oxide on Ag catalysts is well known [10,11]. While adsorption of C_2H_4 on clean [10-13], Cl- and O-covered Ag(110) [10] has been studied, little attention has been paid to Ag(111) [14]. Our earlier studies of hydrocarbon fragments (C_nH_m) [3, 4, 15-17] indicate that Ag(111) is relatively unique among transition metal surfaces; C-C and C-H bond formation from surface C_nH_m fragments and H atoms have much lower activation energies than C-C and C-H bond dissociation. As one interesting example, the dissociation of benzene on Ag(111), induced by electrons (≤ 50 eV) [3], leads to surface phenyl and hydrogen, and during subsequent TPD these recombine to form biphenyl and dihydrogen. The results of this paper demonstrate that bond-specific

electron-induced dissociation may be a general phenomenon that deserves considerable study.

References:

- [1] See recent reviews: Zhou, X.-L.; Zhu, X.-Y.; White, J. M. *Acc. Chem. Res.* **1990**, *23*, 327; *Surface Sci. Rep.* **1991**, *13*, 73.
 - [2] Zhou, X.-L.; Coon, S. R.; White, J. M. *J. Chem. Phys.* **1990**, *92*, 1498.
 - [3] Zhou, X.-L.; Castro, M. E.; White, J. M. *Surface Sci.* **1990**, *238*, 215.
 - [4] Zhou, X.-L.; White, J. M. *J. Chem. Phys.* **1990**, *92*, 5612.
 - [5] Ceyer, S. T. *Langmuir*. **1990**, *6*, 82.
 - [6] (a) Zaera, F. J. *Phys. Chem.* **1990**, *94*, 8350.
 (b) Henderson, M. A.; Mitchell, G. E.; White, J. M. *Surf. Sci.* **1987**, *184*, L325.
 (c) Zhou, X.-L.; White, J. M. *J. Phys. Chem.* **1991**, *95*, 5575.
 (d) Jenks, C. J.; Lin, J.-L.; Chiang, C.-M.; Kang, L.; Leang, P. S.; Wentzlaff, T. H.; Bent, B. E. *Proceedings of the ACS Symposium on Structure-Activity Relationships in Heterogeneous Catalysis*, 199th ACS National Meeting, Boston, **1990**, in press.
 - [7] Liu, Z.-M.; Zhou, X.-L.; Buchanan, D. A.; Kiss, J.; White, J. M. *J. Am. Chem. Soc.* (in press).
 - [8] (a) Lloyd, K. G.; Roop, B.; Campion, A.; White, J. M. *Surf. Sci.* **1989**, *214*, 227.
 (b) Zhou, X.-L.; White, J. M. *Surf. Sci.* **1991**, *241*, 244.
 (c) Zhou, Y.; Feng, W. M.; Henderson, M. A.; Roop, B.; White, J. M. *J. Am. Chem. Soc.* **1988**, *110*, 4447.
 - [9] Zaera, F. J. *Am. Chem. Soc.* **1989**, *111*, 4240.
 - [10] Campbell, C. T.; Paffett, M. T. *Appl. Surface Sci.* **1984**, *19*, 28.
 - [11] Campbell, C. T.; Paffett, M. T. *Surface Sci.* **1984**, *139*, 396.
 - [12] Kruger, B.; Benndorf, C. *Surface Sci.* **1986**, *178*, 704.
 - [13] Backx, C.; de Groot, C. P. M.; Biloen, P. *Appl. Surface Sci.* **1980**, *6*, 256.
 - [14] Felter, T. E.; Weinberg, W. H.; Zhdan, P. A.; Boreskov, G. K. *Surface Sci.* **1980**, *97*, L313
 - [15] Zhou, X.-L.; Solymosi, F.; Blass, P. M.; Cannon, K. C.; White, J. M. *Surface Sci.* **1989**, *219*, 294.
 - [16] Zhou, X.-L.; White, J. M. *Catal. Letters* **1989**, *2*, 375.
 - [17] Zhou, X.-L.; Blass, P. M.; Koel, B. E.; White, J. M. *Surface Sci.* (submitted).
-

Electron-induced chemistry of alkyl chlorides. We have studied the low energy (50 eV) electron induced dissociation (EID) of methyl chloride (CH_3Cl) adsorbed on clean, Cl- and D-covered Ag(111) at 100 K. EID of both submonolayer and multilayer CH_3Cl on Ag(111) occurs very efficiently and results in both retention and desorption of products. For 1 ML, electron-driven desorption is dominated by CH_3 radicals; CH_4 , C_2H_5 and C_2H_6 , but no H_2 , are also observed. During TPD, H_2 , CH_4 , C_2H_4 , C_2H_6 , C_3H_6 , C_3H_8 , C_4H_8 and C_4H_{10} desorb below 350 K and AgCl above 700 K. After TPD to 950 K, surface carbon is found only for very high $\text{EF} \geq 3.37 \times 10^{16} \text{ e}^-$. For multilayers, electron-driven desorption includes, in addition to the species noted for 1 ML, H_2 , Cl, HCl and CH_3Cl . Below 350 K, the only new TPD product is HCl. However, above 400 K new H_2 and HCl TPD peaks appear, and surface carbon is left after TPD.

We have also examined $\text{C}_2\text{H}_5\text{Cl}$ on clean, Cl- and D-covered Ag(111) at 100 K

using TPD, XPS, UPS and $\Delta\Phi$ [1]. $\text{C}_2\text{H}_5\text{Cl}$ adsorbs molecularly at 100 K and desorbs at 124 K (multilayer) and 154 K (monolayer) with no detectable thermal decomposition[2]. For monolayer (ML) coverage, the electron induced dissociation (EID) cross section has an upper limit of $(6\pm 1)\times 10^{-16} \text{ cm}^2$. For coverages up to 1 ML, C_2H_5 radicals and C_2H_6 and C_2H_4 molecules, but no H_2 or Cl-containing species, desorb during electron exposure. At the surface, H and Cl atoms, C_2H_x ($x=3-5$) radicals, and C_2H_4 , C_4H_6 , C_4H_8 and C_4H_{10} molecules are synthesized and retained. Their relative concentrations depend on the electron exposure. There is no evidence for electron-driven C-C bond breaking, except for very high electron doses. In post-EID TPD, synthesized molecules, C_2H_4 , C_4H_6 , C_4H_8 and C_4H_{10} , desorb, whereas H atoms and C_2H_x ($x=3-5$) radicals recombine to produce H_2 , C_2H_4 , C_2H_6 , 1,3-butadiene, butene and *n*-butane, all below 400 K. There are no C_1 's or C_3 's. The only other TPD product is AgCl (750 K) and, unless the electron dose is very high, TPD to 950 K leaves a clean surface. In the presence of coadsorbed Cl, the TPD production of saturated hydrocarbons is suppressed and the desorption of olefins, C_2H_4 , C_4H_6 and C_4H_8 , shifts to a lower temperature. When atomic D is preadsorbed, C-D bonds form both during irradiation and during TPD, producing reaction-limited $\text{C}_2\text{H}_2\text{D}_2$, $\text{C}_2\text{H}_4\text{D}_2$ and $\text{C}_2\text{H}_5\text{D}$, and desorption-limited $\text{C}_4\text{H}_8\text{D}_2$ and $\text{C}_4\text{H}_9\text{D}$.

Multilayers are different. AgCl desorption is sharply suppressed above 2 ML and not detected above 4 ML initial $\text{C}_2\text{H}_5\text{Cl}$ coverage. During electron irradiation, H_2 , C_2H_4 , C_2H_5 , C_2H_6 , C_4H_8 , C_4H_{10} , Cl, HCl and $\text{C}_2\text{H}_5\text{Cl}$ desorb. The post-EID TPD products below 350 K are desorption-limited HCl, H_2 , C_2H_4 , C_4H_6 , C_4H_8 and C_4H_{10} , and reaction-limited C_2H_6 and C_4H_6 . At higher temperatures, HCl and H_2 , not AgCl, desorb and surface carbon is retained after TPD to 950 K. These are ascribed to decomposition of a hydrogen-deficient strongly bound $\text{C}_x\text{H}_y\text{Cl}_z$ ($x>2$) species.

The EID process for $\text{C}_2\text{H}_5\text{Cl}$, while distinctive, does show similarities to that for CH_3Cl . For 1 ML $\text{C}_2\text{H}_5\text{Cl}$ on clean Ag(111), the EID cross section equals that for CH_3Cl and is no larger than $(6\pm 1)\times 10^{-16} \text{ cm}^2$. C_2 alkyl fragments and C_2 hydrocarbons, but no Cl-containing species, are detected during irradiation. Unlike multilayer CH_3Cl , AgCl production is completely inhibited for ≥ 4 ML of $\text{C}_2\text{H}_5\text{Cl}$. As for CH_3Cl , preadsorbed Cl alters EID. Throughout these experiments, EID of C-C bonds is a minor process and is detectable only at $EF \geq 1.57 \times 10^{16} \text{ e}^-$.

References:

- [1] X.-L. Zhou, P. M. Blass, B. E. Koel and J. M. White, Surface Sci. (submitted).
- [2] X.-L. Zhou and J. M. White, Surface Sci. 241 (1991) 259.

Azomethane. Azo compounds are promising precursors for the synthesis of important intermediates on metal surfaces. The photon-assisted adsorption of $\text{CF}_3\text{N}_2\text{CF}_3$ has been studied on Si(111) and SiO [1] and the thermal [2] and photon [3] induced chemistry of azomethane has been recently explored on Pd(111). In the latter, $\text{CH}_3\text{N}_2\text{CH}_3$ undergoes partial thermal decomposition. H_2 and HCN are the main products observed in TPD. No photochemistry of chemisorbed $\text{CH}_3\text{N}_2\text{CH}_3$ has been observed, although the second layer is photolyzed with partial retention of the methyls and desorption of N_2 .

The thermal and electron-induced chemistry of $\text{CH}_3\text{N}_2\text{CH}_3$ on Ag(111) has been studied using TPD, XPS and AES. $\text{CH}_3\text{N}_2\text{CH}_3$ adsorption on Ag(111) is completely reversible, with desorption peaks at 180 and 130 K for monolayer and multilayer, respectively. Electron irradiation on 1 ML of $\text{CH}_3\text{N}_2\text{CH}_3$ results in almost quantitative electron stimulated desorption (ESD) of N_2 . ESD of CH_3 and CH_4 , as well as traces of C_2H_6 and C_2H_2 , is also observed. The retained fragments desorb in TPD mainly as H_2 and CH_4 . At (54.7 ± 0.3) eV, the EID cross section is about $7 \times 10^{-17} \text{ cm}^2$. The EID cross section increases with electron energy and has a threshold of about 10 eV. The EID is attributed to ionization of chemisorbed azomethane.

References:

- [1] F. R. McFeely, J. A. Yarmof, A. Taleb-Ibrahmi and D. B. Beach *Surf. Sci.* 206 (1988) 371.
 - [2] L. Hanley, X. Guo, and J. T. Yates, *J. Phys. Chem.* 93 (1989) 6574.
 - [3] L. Hanley, X. Guo, and J. T. Yates, *Surf. Sci.* 232 (1990) 129.
-

6.4. Photon activation.

Sulfur dioxide. Sulfur dioxide, important in certain environmental issues, has a rich and complex photochemistry and photophysics. Thus, from many perspectives it is an interesting adsorbate. On Ag(111), it adsorbs and desorbs reversibly; monolayers desorb at 180 K and multilayers at 130 K. The photochemistry ($h\nu \leq 5.3$ eV) of monolayer SO_2 on Ag(111) is simple; there is no dissociation and no reaction with neighboring molecules, only photon-induced desorption occurs. The photodesorption rate is first order in the photon flux, increases linearly up to 1 ML but then decays sharply, indicating that excitation is substrate-mediated, i.e., the photons absorbed by the metal excite electrons which attach themselves to SO_2 . The resulting short-lived anion is drawn toward the metal by electrostatic interactions and, upon relinquishing its charge back to the metal, the SO_2

finds itself in a very repulsive region with respect to the adsorbate-substrate bond. Thus, desorption occurs easily. For coverages up to 1 ML, the time averaged photodesorption cross section is of order 10^{-20} cm². More recent work shows that the differential cross section drops sharply in the early stages of photolysis, an effect attributed to subtle photon-driven structural changes in the adsorbed SO₂.

Alkyl halide photochemistry. There are a number of reports on the UV photochemistry of molecule/metal systems from other research laboratories [1-29]. It is now clear that photochemistry, particularly bond dissociation, can compete effectively with quenching for molecules which, in their ground states, are weakly held on metal surfaces and which readily photodissociate in the gas phase. Compared to gas phase photochemistry, surface photochemistry is more complicated because the surface can play a very important role by perturbing, promoting, or inhibiting processes [15,16,18]. In many cases, photo-excited substrate electrons are believed to be responsible for the observed chemistry [7,10,12,14,18,19,26,30].

Ethyl Chloride. The photochemistry of C₂H₅Cl on Pt(111) at 100 K has been reported earlier [1]. It dissociates to ethyl (C₂H₅) and Cl near 5 eV. Methyl chloride (CH₃Cl) on Pt(111) [4] and Ni(111) [18] also readily photodissociates to CH₃ and Cl. Photodissociation of other molecules containing C-Cl bonds, such as ClCH₂CH₂Cl on Pt(111) [17] and chloro-benzene on Ag(111) [13], has been reported.

In the gas phase, the photochemistry of CH₃Cl has been more thoroughly studied than C₂H₅Cl but the photochemistry is analogous [31]. In the near UV region, RCl is excited to a repulsive state via electronic promotion from a Cl non-bonding orbital, $n(\text{Cl})$, to a C-Cl antibonding orbital, σ^* . The result is C-Cl bond cleavage. The optical absorption cross section of CH₃Cl decreases from about 1×10^{-18} cm² at 173 nm to $< 10^{-23}$ cm² at $\lambda > 240$ nm [31]. The absorption spectrum of C₂H₅Cl in alcohol solution is nearly identical to that of CH₃Cl in the gas phase [31,32].

We have examined the photochemistry of ethyl chloride, methyl bromide and methyl iodide on Ag(111). Ethyl, instead of methyl, chloride was used because methyl chloride does not adsorb on Ag(111) at 100 K. Thermally, desorption of adsorbed C₂H₅Cl occurs molecularly at 124 K (physisorbed) and 154 K (chemisorbed) and there is no detectable decomposition. UV irradiation leads to bond breaking, interpreted by analogy with well-established literature, in terms of C-Cl cleavage. While some hydrocarbon fragments, probably C₂H₅, desorb during irradiation, a fraction is retained and recombines to form butane (C₄H₁₀) in post-irradiation TPD. There is no evidence for C-C or C-H bond breaking. All Cl accumulates on the surface and desorbs as AgCl above 700 K in post-

irradiation TPD. There is no photodesorption of molecular C_2H_5Cl . The cross section for the photodissociation of a chemisorbed monolayer of C_2H_5Cl is $\sim 2.6 \times 10^{-20} \text{ cm}^2$ at 254 nm (4.9 eV). It decreases with increasing wavelength and has a threshold of 350-380 nm (3.3-3.5 eV). The average photolysis cross-section decreases with increasing initial C_2H_5Cl coverages. For physisorbed multilayers, the photodissociation has a lower rate and higher threshold (~ 4.1 eV). The thresholds for both physisorbed and chemisorbed C_2H_5Cl are lower than for gas phase photodissociation. The results are discussed in terms of substrate excitation processes, quenching by the substrate and by neighboring adsorbed molecules, and the inactivity of Ag toward C-C and C-H bond breaking.

References:

- [1] K. G. Lloyd, B. Roop, A. Campion and J. M. White, *Surface Sci.* **214** (1989) 227.
K. G. Lloyd, A. Campion and J. M. White, *Catal. Lett.* **2** (1989) 105.
- [2] S. A. Costello, B. Roop, Z.-M. Liu and J. M. White, *J. Phys. Chem.* **92** (1988) 1019.
Y. Zhou, W. M. Feng, M. A. Henderson, B. Roop and J. M. White, *J. Am. Chem. Soc.* **110** (1988) 4447.
Z.-M. Liu, S. A. Costello, B. Roop, S. R. Coon, S. Akhter and J. M. White *J. Phys. Chem.* **93** (1989) 7681.
- [3] Z.-M. Liu, S. Akhter, B. Roop and J. M. White, *J. Am. Chem. Soc.* **110** (1988) 8708.
- [4] B. Roop, S. A. Costello, Z.-M. Liu and J. M. White, *Proc. XIX Solvay Conf.* **14** (1988) 343.
B. Roop, K. G. Lloyd, S. A. Costello, A. Campion and J. M. White, *J. Chem. Phys.* **91** (1989) 5103.
- [5] S. Hatch, X.-Y. Zhu, A. Campion and J. M. White, *J. Chem. Phys.* (submitted).
- [6] X.-Y. Zhu, S. Hatch, A. Campion and J. M. White, *J. Chem. Phys.* **91** (1989) 5011.
- [7] S. Hatch, X.-Y. Zhu, J. M. White, and A. Campion, *J. Chem. Phys.* **92** (1990) 2681.
- [8] X.-L. Zhou and J. M. White, *Desorption Induced by Electronic Transition, DIET IV*, Eds. G. Betz and P. Varga (1989) 80.
- [9] B. Roop, S. A. Costello, C. M. Greenlief and J. M. White, *Chem. Phys. Lett.* **143** (1988) 38.
- [10] X.-L. Zhou and J. M. White, *J. Chem Phys.* **92** (1990) 1504.
- [11] X.-L. Zhou and J. M. White, *J. Phys. Chem.* **94** (1990) 2643.
- [12] X.-L. Zhou and J. M. White, *Chem. Phys. Lett.* **167** (1990) 205.
- [13] X.-L. Zhou and J. M. White, *J. Chem. Phys.* **92** (1990) 5612.
- [14] E. Hasselbrink, S. Jakubith, S. Nettesheim, M. Wolf, A. Cassuto and G. Ertl, *J. Chem. Phys.* **92** (1990) 3154.
- [15] T. J. Chuang, *Surface Sci. Rep.* **3** (1983) 1.
- [16] E. P. Marsh, M. R. Schneider, T. L. Gilton, F. L. Tabares, W. Meier and J. P. Cowin, *Phys. Rev. Lett.* **60** (1988) 2251.
E. P. Marsh, F. L. Tabares, M. R. Schneider and J. P. Cowin, *J. Vac. Sci. Technol. A* **5** (1987) 519.
E. P. Marsh, F. L. Tabares, M. R. Schneider, T. L. Gilton, W. Meier, and J. P. Cowin, *J. Chem. Phys.* **92** (1990) 2004.
- [17] V. H. Grassian and G. C. Pimental, *J. Chem. Phys.* **88** (1988) 4484.
- [18] E. P. Marsh, T. L. Gilton, W. Meier, M. P. Schneider and J. P. Cowin, *Phys. Rev. Lett.* **61** (1988) 2725.
T. L. Gilton, C. P. Dehnhostel and J. P. Cowin, *J. Chem. Phys.* **91** (1989) 1937.
- [19] S. A. Buntin, L. J. Richter, R. R. Cavanagh and D. A. King, *J. Chem. Phys.* **89** (1988) 5344. S. A. Buntin, L. J. Richter, D. A. King and R. R. Cavanagh, *J. Chem. Phys.* **91** (1989) 6429.
- [20] F. G. Celli, P. M. Whitmore and K. C. Janda, *Chem. Phys. Lett.* **138** (1989) 5011.
- [21] T. A. Germer and W. Ho, *J. Chem. Phys.* **89** (1988) 562.
- [22] K. Domen and T. J. Chuang, *J. Chem. Phys.* **90** (1989) 3332. *Phys. Rev. Lett.* **59** (1987) 1484.
- [23] A. Modl, K. Domen and T. J. Chuang, *Chem. Phys. Lett.* **154** (1989) 187.
- [24] L. Hanley, X. Guo and J. T. Yates, Jr., *J. Chem. Phys.* **91** (1989) 7720.

- [25] G. M. Goncher, C. A. Parsons and C. B. Harris, *J. Phys. Chem.* **88** (1984) 4200.
 [26] C. C. Cho, B. A. Collings, R. E. Hammer, J. C. Polanyi, C. D. Stanners, J. H. Wang and G.-X. Xu, *J. Phys. Chem.* **93** (1989) 7761.
 [27] J. Yoshinobu, X. Guo, and J. T. Yates, Jr., *J. Chem. Phys.* (submitted).
 [28] M. Wolf, S. Nettesheim, J. M. White, E. Hasselbrink, and G. Ertl, *J. Chem. Phys.* **92** (1990) 1509.
 [29] L. Hanley, X. Guo And J. T. Yates, Jr., *J. Chem. Phys.* **91** (1989) 7220.
 [30] Ph. Avouris and R. E. Walkup, "*Annual Review of Physical Chemistry*" **40** (1989) 1.
 [31] H. Okabe, "*Photochemistry of Small Molecules*" (Wiley-Interscience, New York, 1978).
 [32] J. G. Calvert and J. N. Pitts, Jr., "*Photochemistry*" (Wiley-Interscience, New York, 1966).

Methyl bromide. The gas phase UV photochemistry of CH₃Br has been well studied [1,2]. The absorption in the near UV region is assigned to $n(\text{Br}) \rightarrow \sigma^*$ transition involving promotion of lone pair electrons centered on Br to a C-Br antibonding (σ^*) orbital. The absorption cross section maximizes ($1 \times 10^{-18} \text{ cm}^2$) at 203 nm and decreases smoothly, by extrapolation, to $< 5 \times 10^{-24} \text{ cm}^2$ at $\lambda > 300 \text{ nm}$. The primary process in the gas phase is dissociative:

On Ag(111) at 100 K, CH₃Br adsorbs and desorbs molecularly with no thermal decomposition. The adsorption is through the Br atom and lowers work function by ~1.0 eV at monolayer and ~0.7 eV at multilayer coverages. UPS indicates that adsorbed CH₃Br is not strongly distorted compared to the gas phase. The surface density at 1 ML is $\sim 4.6 \times 10^{14} \text{ molecules/cm}^2$. Photon irradiation causes C-Br bond cleavage; all Br and a small portion of CH₃ are retained at the surface. There is no photodesorption of molecular CH₃Br. In post-irradiation TPD, all the retained CH₃ fragments recombine to form C₂H₆ below 300 K and surface Br desorbs as AgBr above 700 K. The photodissociation threshold for the first layer (chemisorbed) is ~3.0 eV and the second layer (physisorbed) is >3.5 eV, both lower than in the gas phase (~4.5 eV). The cross section for the photodissociation of 1 ML CH₃Br as a function of wavelength is estimated. Compared to the gas phase, the photodissociation cross section for chemisorbed CH₃Br is much larger, while that for physisorbed CH₃Br is slightly larger. The average effective photolysis rate decreases with increasing initial CH₃Br coverage.

The photochemistry of CH₃Br on Pt(111) [3,4] and Br/Ni(111) [5] has been reported previously. The C-Br bond of chemisorbed CH₃Br on Pt(111) is readily photodissociated, producing Br(a) and CH₃(a), even at wavelengths significantly red-shifted compared to the gas phase. However, when CH₃Br is separated from Pt(111) by 1 ML of carbide carbon, where CH₃Br is weakly physisorbed, the red-shift is removed and the average photolysis yield is reduced [4]. The removal of the red-shift on carbon-

covered Pt(111) is attributed to either (1) loss of stabilizing excited state interactions with Pt(111) or (2) a much lower cross section for dissociative electron capture in the physisorbed multilayer than in the chemisorbed monolayer. At 5 eV, the dissociation of CH₃Br on Br/Ni(111) has been attributed to the dissociative electron attachment of substrate-excited electrons [5]. At higher energy (6.4 eV), Marsh et al. [5] report that photofragmentation to CH₃ and Br, of CH₃Br on Br/Ni(111) takes place from submonolayer to 10 monolayer coverages, that the photodynamics is strongly perturbed by the substrate, that the photofragmentation is dominated by direct excitation but may also involve dissociative electron attachment (DEA), and that the cross section is 4-12 times lower, depending on the CH₃Br coverage, than for gas phase photolysis.

References:

- [1] K. Okabe, *"Photochemistry of Small Molecules"* (Wiley-Interscience, New York, 1978)
 - [2] J. G. Calvert and J. N. Pitts, Jr., *"Photochemistry"* (Wiley-Interscience, New York, 1966)
 - [3] S. A. Costello, B. Roop, Z.-M. Liu and J. M. White, *J. Phys. Chem.* **92** (1988) 1019.
Y. Zhou, W. M. Feng, M. A. Henderson, B. Roop and J. M. White, *J. Am. Chem. Soc.* **110** (1988) 4447.
 - Z.-M. Liu, S. A. Costello, B. Roop, S. R. Coon, S. Akhter and J. M. White, *J. Phys. Chem.* **93** (1989) 7681.
 - [4] S. Hatch, X.-Y. Zhu, A. Campion and J. M. White, unpublished.
 - [5] E. P. Marsh, M. R. Schneider, T. L. Gilton, F. L. Tabares, W. Meier and J. P. Cowin, *Phys. Rev. Lett.* **60** (1988) 2251.
E. P. Marsh, F. L. Tabares, M. R. Schneider and J. P. Cowin, *J. Vac. Sci. Technol. A* **5** (1987) 519.
E. P. Marsh, F. L. Tabares, M. R. Schneider, T. L. Gilton, W. Meier and J. P. Cowin, *J. Chem. Phys.* **92** (1990) 2004.
-

Methyl Iodide. The gas phase UV photochemistry of CH₃I has been well studied [1,2]. The absorption in the near UV region is assigned to $n(I) \rightarrow \sigma^*$ transition (lone pair to antibonding C-I orbital). The absorption cross section maximum ($1.5 \times 10^{-18} \text{ cm}^2$) occurs at 258 nm and decreases, by extrapolation, to $<10^{-23} \text{ cm}^2$ at $\lambda > 360 \text{ nm}$. The primary photodissociation process in the gas phase is

While adsorbed CH₃I does not dissociate thermally at 100 K, it is easily photodissociated. Upon the C-I bond cleavage, all I and a small portion of CH₃ are retained at the surface; most CH₃ desorbs during UV irradiation. There is no photodesorption of molecular CH₃I. The photodissociation threshold is ~2.6 eV for chemisorbed monolayer CH₃I and ~3.6 eV for physisorbed multilayer CH₃I. Substrate quenching of the photodissociation is observed for the chemisorbed CH₃I.

The photochemistry of CH_3I on $\text{Pt}(111)$ [3] has been reported previously. With a high pressure Hg arc lamp, C-I bond cleavage occurs readily, producing $\text{CH}_3(\text{a})$ and $\text{I}(\text{a})$. Monolayer CH_3I is photolyzed at a slower rate than the physisorbed multilayer, a fact attributed to faster electronic quenching for the monolayer. In related work, Chuang and co-workers studied laser-induced photodissociation and desorption of another iodide, CH_2I_2 , on Al films, Ag films and $\text{Ag}(110)$ [4]. They observed photodissociation of CH_2I_2 on Al at both submonolayer and multilayer coverages with a 308 nm laser, and laser induced thermal desorption with a 532 nm laser. On Ag and with a 308 nm laser, however, they observed little photochemical effect at submonolayer coverages. They attributed the photodissociation to direct excitation and the absence of a photo-effect on submonolayer CH_2I_2 to rapid electronic relaxation and/or a low absorption coefficient.

CH_3I adsorbs molecularly on $\text{Ag}(111)$ at 100K[5]. Both molecular desorption and dissociation are evident in TPD. Thermal dissociation occurs above 120-130 K and produces $\text{CH}_3(\text{a})$ and $\text{I}(\text{a})$. $\text{CH}_3(\text{a})$ recombines to form C_2H_6 at 257 K and $\text{I}(\text{a})$ desorbs atomically above 700 K. A maximum of 0.35 ML dissociates. As expected, CH_3I adsorbs through the I atom and lowers the work function of $\text{Ag}(111)$ by 1.25 eV at monolayer and 1.05 eV at multilayer coverages. UPS indicates that adsorbed CH_3I is not significantly distorted compared to the gas phase. The surface density at 1 ML is $\sim 4.6 \times 10^{14}$ molecules/ cm^2 . Since CH_3I dissociates thermally on $\text{Ag}(111)$ above 120 K, monolayer CH_3I must be irradiated and analyzed at lower temperature (~ 100 K) to avoid thermal effects.

Comparing the three halides, for photon energies where all three molecules are active, the initial photolysis rates at 1 ML are ordered: $\text{CH}_3\text{I} > \text{CH}_3\text{Br} > \text{C}_2\text{H}_5\text{Cl}$. The extent of the red-shift is $\text{CH}_3\text{I} < \text{CH}_3\text{Br} < \text{C}_2\text{H}_5\text{Cl}$. The photochemistry in the red-shifted region is ascribed to substrate-mediated excited electrons which attach to the halides, which then dissociate. For the iodide, direct photon absorption by the adsorbate-substrate complex and physisorbed adsorbate probably make a contribution below 350 nm.

References:

- [1] H. Okabe, "*Photochemistry of Small Molecules*" (Wiley-Interscience, New York, 1978).
 - [2] J. G. Calvert and J. N. Pitts, Jr., "*Photochemistry*" (Wiley-Interscience, New York, 1966).
 - [3] Z.-M. Liu, S. Akhter, B. Roop and J. M. White, *J. Am. Chem. Soc.* **110** (1988) 8708.
 - [4] K. Domen and T. J. Chuang, *J. Chem. Phys.* **90** (1989) 3332.
 - [5] X.-L. Zhou, F. Solymosi, P. M. Blass, K. C. Cannon and J. M. White, *Surface Sci.* **219**(1989) 294.
-

Publications (1989-1992) acknowledging DOE support.

1. K. C. Cannon and J. M. White, "The Surface Chemistry of Isolated and Aggregated Silica-bound Rhodium Complexes," *J. Catal.* **120** (1989) 314.
2. J. M. White, "SIMS of Coadsorbed Layers Involving Potassium," in Physics and Chemistry of Alkali Adsorption, eds. H. P. Bonzel, A. M. Bradshaw, G. Ertl (Elsevier, 1989) 231.
3. Y. Zhou, M. A. Henderson, W. M. Feng, and J. M. White, "Decomposition of Methyl Iodide on Ru(001)," *Surface Sci.* **224** (1989) 386.
4. E. Auschitzky, A. B. Boffa, J. M. White, and T. Sahin, "Adsorption of H₂O and H₂S on Thin Films of Cobalt Oxide Supported on Alumina," *J. Catal.* **125** (1990) 325.
5. X.-L. Zhou and J. M. White, "Surface Photochemistry: 14. Monolayer versus Multilayer for Alkyl Halides on Ag(111)," *Chem. Phys. Lett.* **167** (1990) 205.
6. X.-L. Zhou and J. M. White, "Alkyl Halide Photochemistry on Ag(111): I. Ethyl Chloride," *Surface Sci.* **241** (1991) 244.
7. X.-L. Zhou and J. M. White, "Alkyl Halide Photochemistry on Ag(111): II. Methyl Bromide," *Surface Sci.* **241** (1991) 259.
8. X.-L. Zhou and J. M. White, "Alkyl Halide Photochemistry on Ag(111): III. Methyl Iodide," *Surface Sci.* **241** (1991) 270.
9. D. A. Buchanan, M. E. Hernandez, F. Solymosi and J. M. White, "CO-Induced Structural Changes of Rh on TiO₂ Support," *J. Catal.* **125** (1990) 456.
10. J. M. White, "Photochemistry at Surfaces," in Eighteen Years of Colloid and Surface Chemistry: The Kendall Award Addresses, ed. T. Fort and K. Y. Mysels (ACS: Washington, 1991), 367.
11. X.-L. Zhou, M. E. Castro and J. M. White, "Interactions of UV Photons and Low Energy Electrons with Chemisorbed Benzene on Ag(111)," *Surface Sci.* **238** (1990) 215.
12. X.-L. Zhou, X.-Y. Zhu and J. M. White, "Photodissociation of Intra-Adsorbate Bonds at Adsorbate-Metal Interfaces," *Acc. Chem. Res.* **23** (1990) 327.
13. Z. M. Liu, Y. Zhou, F. Solymosi and J. M. White, "Spectroscopic Study of K-Induced Activation of CO₂ on Pt(111)," *Surf. Sci.* **245** (1991) 289.
14. X.-L. Zhou, S. R. Coon, and J. M. White, "Potassium-Promoted Decomposition of Methyl Bromide on Ag(111)," *J. Chem. Phys.* **94** (1991) 1613.
15. X.-L. Zhou and J. M. White, "Reactions of C₂H₃I, n-C₃H₇I, ClCH₂I and Cl(CH₂)₃I Adsorbed on Ag(111)," *J. Phys. Chem.* **95** (1991) 5575.
16. M. E. Castro and J. M. White, "Photochemistry of SO₂ on Ag(111)," *J. Chem. Phys.* **95** (1991) 6057.

17. X.-L. Zhou and J. M. White, "Low Energy Electron-Induced Chemistry of Ethylene on Clean, Cl and D-Covered Ag(111)," J. Phys. Chem. (in press).
18. G. E. Poirier and J. M. White, "Identification of the Facet Planes of Phase I TiO₂(001) Rutile by Scanning Tunneling Microscopy and Low Energy Electron Diffraction," J. Vac. Sci. and Tech. B 10/1 (1992) 6.
19. Z.-M. Liu, X.-L. Zhou, D. A. Buchanan, J. Kiss and J. M. White, "The Surface Chemistry on Vinyl Iodide on Pt(111)," JACS 114 (1992) 2031.
20. X.-L. Zhou, P. M. Blass, B. E. Koel and J. M. White, "Low Energy Electron Induced Chemistry: CH₃Cl on Ag(111)," Surf Sci. (in press).
21. X.-L. Zhou, P. M. Blass, B. E. Koel and J. M. White, "Low Energy Electron Induced Chemistry: C₂H₅Cl on Ag(111)," Surf. Sci. (in press).
22. Diann J. Alberas, J. Kiss, X.-M. Liu and J. M. White, "Surface Chemistry of Hydrazine on Pt(111)," Surf. Sci. (submitted).
23. X.-L. Zhou, Z.-M. Liu and J. M. White, "Conversion of Vinyl to Ethylidyne on Pt(111)," Chem. Phys. Letts. (in press).
24. J. M. White, "Molecular Photochemistry on Surfaces: Role of Adsorbate-Substrate Structure," presented at DIET V meeting, Santa Fe, NM, April 1992.

END

**DATE
FILMED**

11 / 20 / 92