REPORT

QUARTERLY TECHNICAL PROGRESS

REPORT NO. 4 (FINAL)

PELLETIZING/ RESLURRYING AS A MEANS OF DISTRIBUTING AND FIRING CLEAN COAL

Received by OSTI
JUL 23 1992

To

U.S. DEPARTMENT OF ENERGY

PITTSBURGH ENERGY TECHNOLOGY CENTER

SEPTEMBER 20, 1991

Battelle

Putting Technology To Work

**PELLETIZING/RESLURRYING AS A MEANS OF
DISTRIBUTING AND FIRING CLEAN COAL**

Contract No. DE-AC22-90PC90166

Contract Period: August 3, 1990 to August 2, 1992

**Final
Quarterly Technical Progress Report No.4**

Period Covered by Report: April 1, 1991 to June 30, 1991

**Battelle
505 King Avenue
Columbus, Ohio 43201-2693**

Principal Investigator: H. Nicholas Conkle Phone No. (614) 424-5616

Date Submitted: September 20, 1991

Prepared for

PETC Project Manager: Anthony E. Mayne

**Pittsburgh Energy Technology Center
U. S. Department of Energy
P. O. Box 10940
Pittsburgh, Pennsylvania 15236**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

This report is a work prepared for the United States by Battelle. In no event shall either the United States or Battelle have any responsibility or liability for the consequences of any use, misuse, inability to use, or reliance upon the information contained herein, nor does either warrant or otherwise represent in any way the accuracy, adequacy, efficacy, or applicability of the contents hereof.

TABLE OF CONTENTS

	<u>Page</u>
EXECUTIVE SUMMARY	1
OBJECTIVE	1
PROJECT DESCRIPTION	2
PROJECT STATUS	3
Task 2 - Prepare and Test Small Batches	3
Reconstitution	3
Slurry Formulation	6
Slurry Atomization	23
Selected Processes for Task 3 Evaluation	27
Tasks 3 through 7	27
Task 8 - Utilization/Commercialization	27
Task 9 - Prepare Additional Cake	28
PLANNED FUTURE ACTIVITIES	29
SUMMARY	32
APPENDIX A RECONSTITUTION DATA BASE	
APPENDIX B SLURRY FORMULATION DATA BASE	
APPENDIX C ATOMIZATION OF THREE BATTELLE COAL-WATER FUELS	
APPENDIX D COAL ANALYSES	

LIST OF TABLES

	<u>Page</u>
TABLE 1. EFFECT OF HEATING ON THE VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO. 6 PELLETS	8
TABLE 2. BENCH SLURRY PREPARATION TESTS	14
TABLE 3. PARTICLE SIZE DISTRIBUTIONS OF RESLURRIED FILTER CAKE AND PELLETS PREPARED FROM ULTRA-FINE ILLINOIS No. 6 COAL	15
TABLE 4. PARTICLE SIZE DISTRIBUTIONS OF RESLURRIED PELLETS PREPARED FROM ULTRA-FINE UPPER ELKHORN COAL	15
TABLE 5. RESULTS OF DILUTION TESTS ON RESLURRIED ILLINOIS NO. 6 SPHERES (ORIGINAL SLURRIES STORED FOR ABOUT 1 MONTH)	18
TABLE 6. COMPARISONS OF SLURRY VISCOSITIES BEFORE AND AFTER ONE-MONTH STORAGE	21
TABLE 7. EFFECT OF INCREMENTAL A-23 ADDITIONS ON THE VISCOSITY OF FRESH SLURRY PREPARED FROM AIR-DRIED PELLETS CONTAINING CORN STARCH BINDER	21
TABLE 8. ANALYSIS OF CLEANED ILLINOIS AND UTAH COAL	27

LIST OF FIGURES

FIGURE 1. PROJECT CONCEPT	2
FIGURE 2. WORK BREAKDOWN STRUCTURE AND SCHEDULE	4
FIGURE 3. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM ILLINOIS No.6 PELLETS CONTAINING LIGNIN SULFONATE BINDER	10
FIGURE 4. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM	10
FIGURE 5. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM ILLINOIS No.6 PELLETS CONTAINING CORN STARCH BINDER	11
FIGURE 6. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING LIGNIN SULFONATE BINDER	11

LIST OF FIGURES
(Continued)

	<u>Page</u>
FIGURE 7. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING SHUR BOND BINDER	12
FIGURE 8. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING CORN STARCH BINDER	12
FIGURE 9. EFFECT OF SMALL DILUTIONS ON THE VISCOSITY OF SLURRIES PREPARED FROM AIR DRIED AND OVEN-DRIED ILLINOIS NO.6 PELLETS PREPARED WITH A CORN STARCH BINDER	19
FIGURE 10. EFFECT OF SMALL DILUTIONS ON THE VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO.6 PELLETS PREPARED WITH A LIGNIN SULFONATE AND SHUR BOND BINDERS	19
FIGURE 11. EFFECT OF INCREASED DISPERSANT DOSAGE ON VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO.6 PELLETS CONTAINING CORN STARCH BINDER	20
FIGURE 12. COAL PELLETS BEING CONVERTED INTO CWF	23
FIGURE 13. SIMPLE 3 PROP PROPELLER USED FOR SLURRY FORMULATION	23
FIGURE 14. SLURRY ATOMIZATION TEST CHAMBER	24
FIGURE 15. CLOSEUP OF ATOMIZED ILLINOIS No. 6 PELLET SLURRY	25

Draft

Quarterly Technical Progress Report No. 4

Contract No. DE-AC22-90PC90166

on

PELLETIZING/RESLURRYING AS A MEANS OF
DISTRIBUTING AND FIRING CLEAN COAL

by

H.N. Conkle, J.K. Raghavan, F.J. Smit, and M.C. Jha

EXECUTIVE SUMMARY

Work in this quarter focused on developing the data to select the best processes, and binders, for large scale production tests. A number of slurry preparation tests were conducted to evaluate the effects of formulation temperature, mixing technique, dilution and dispersant effects, and aging on slurry quality. Based on these tests, preferred formulations recipes were set, and two 200-lb lots of pellets were made for atomization testing. Tests of these two pellet lots, and 200-lb of clean coal filter cake, were conducted by the University of Alabama. They successfully proved that pellets could be formulated into slurry and the slurry atomized easily to produce small droplet sizes.

Future work will concentrate on the production of large batches of clean-coal pellets and evaluation of their properties.

OBJECTIVE

The objective of this study is to develop technology that permits the practical and economic preparation, storage, handling, and transportation of coal pellets, which can be formulated into CWFs suitable for firing in small- and medium-size commercial and industrial boilers, furnaces, and engines.

PROJECT DESCRIPTION

The project includes preparing coal pellets and capsules from wet filter cake that can be economically stored, handled, transported, and slurried into a CWF that can be suitably atomized and fired at the user site. The wet cakes studied are being prepared from ultra-fine (95 % -325 mesh) coal beneficiated by advanced froth-flotation techniques. The coals studied include one eastern bituminous coal from Virginia (Elkhorn), one midwestern coal from Illinois (Illinois No. 6), and one western bituminous coal from Utah (Sky Line coal).

The Battelle/AMAX team is emphasizing two approaches to preparing coal pellets. The first approach is the use of an internal binder to prepare pellets having sufficient strength to be stored, handled, and transported in a manner similar to raw coal. The second approach is to prepare lower-strength pellets that are coated, encapsulated, or pelletized, to form a "coal capsule," or pellet, that can be readily stored, handled, and transported under specialized (i.e., less severe) conditions. In both cases, preference is being given to binders or encapsulation materials that will be desirable components of the additive package used in producing a suitable slurry.

Research activities fall into three major areas:

- Reconstitution
- Storage, Handling, and Transportation
- Coal Water Fuel Formulation.

The project concept, incorporating these three main activities is shown in Figure 1.

FIGURE 1. PROJECT CONCEPT

More specifically the project activities includes the following 10 tasks:

- Task 0 - Acquire Coal (Completed)
- Task 1 - Identify Technology (Completed)
- Task 2 - Prepare and Test Small Batches
- Task 3 - Prepare Bench/Pilot-scale Pellets
- Task 4 - Evaluate Storage Characteristics
- Task 5 - Evaluate Handling Characteristics
- Task 6 - Evaluate Transportation Characteristics
- Task 7 - Reslurry Pellets and Evaluate CWF
- Task 8 - Utilization/Commercialization
- Task 9 - Prepare Additional Cake.

PROJECT STATUS

The project's schedule is shown in Figure 2. Details of the work breakdown structure and the planned duration of the various project activities are included in the figure. Work in this quarter covered Tasks 2 and 9. This status section summarizes activities and accomplishments for the two tasks.

Task 2 - Prepare and Test Small Batches

The objective of this task was to select the best two techniques for each coal for pilot plant testing, based on the "most promising techniques" identified in Task 1. The basis for the selection included both pellet and slurry quality testing. The slurry quality evaluation included both rheological measurements and slurry atomization performance tests. The Task 2 results are presented below by research area: reconstitution, slurry formulation, and slurry atomization.

Reconstitution

Efforts in this quarter centered on completing the reconstitution data base and providing pellets to support the slurry formulation and atomization test efforts. A partial listing of the coal reconstitution data base, for the three coals, including the various processes and binders considered,

<-1990

ACTIVITIES

AUG SEP OCT NOV DEC JAN FEB MAR APR MAY JUN JUL

FIGURE 2. SCHEDULE FOR S. T. & H. OF COALS

<-1991

ACTIVITIES

AUG SEP OCT NOV DEC JAN FEB MAR APR MAY JUN JUL

FIGURE 2. SCHEDULE FOR S. T. & H. OF COALS
(Continued)

was presented in the last quarterly report. Numerous gap existed. Pellet preparation testing had been completed, but pellet quality data was, in some cases, unavailable at the time of the report preparation. The missing data have been determined and the complete data base is presented in Appendix A. The preferred reconstitution techniques remain the same:

- Elkhorn: Roller-and-Die Pelletization and Disk Pelleting
- Illinois No. 6: Roller-and-Die Pelletization and Disk Pelleting
- Utah: Roller-and-Die Pelletization and Extrusion Pelletization.

Preferred binders are pre-gelatinized corn starch, Shur Bond (petroleum based emulsion), and calcium lignin sulfonate.

Slurry Formulation

Various studies were conducted in this quarter to better understand conditions affecting slurry formulation. Specifically, tests were conducted on:

- Rheological Properties
- Temperature Effects
- Mixing Techniques
- Dilution and Dispersant Dosage
- Aging.

Each is discussed below.

Rheological Properties. Like in the reconstitution area, work included completing missing slurry property data in the coal reconstitution data base. The completed data base is included as Appendix B. Slurries prepared from lignin sulfonate-, Shur-Bond-, and corn starch-bound pellets show viscosities below 500 cP, a shear thinning, thixotropic rheology, and good to excellent short term stability.

Temperature Effects. The effect of increasing temperature on viscosity was determined for slurries prepared from six samples of disk pellets of Illinois No. 6 coal. Lignin sulfonate, Shur-Bond, and starch had been used as the binder in the pellets, and air-dried and oven dried samples of the pellets were tested. The tests on each sample were conducted at 20 to 24 C,

42 to 44 C, and 50 to 60 C. The standard amenability test procedure was followed when preparing the slurries, except that splits of the slurries were heated to slightly above the target temperatures while being shaken in a water bath just before the viscosity measurements. An electric heater circulated hot air between the slurry container of the viscometer and a heat shield placed around the container during these measurements in order to maintain the temperature of the slurry.

The measured viscosity of the slurries dropped significantly with increasing temperature, as shown by the measurement given in Table 1. This is to be expected since the viscosity (and density) of water (see data from Lange's Handbook below) decreases with temperature as follows:

Temperature, °C	Viscosity, Centipoise	Density, g/ml
20	1.0050	0.99823
40	0.6560	0.99224
60	0.4688	0.98324

The viscosities of dispersed suspensions are usually evaluated in terms of relative viscosities:

$$\mu_{rel} = \frac{\mu_{slurry}}{\mu_{liquid}}$$

where μ_{rel} is equal to a complex function of particulate loading, dispersion, shape, and size distribution (see Reference 1 below).

¹ F. J. Smit and M. H. Berggren, "Relative Viscosity Correlations of Micronized Coal Water Slurries", Proceedings of the 14th International Conference on Coal and Slurry Technology, Clearwater, Florida, April 24-27, 1989.

TABLE 1. EFFECT OF HEATING ON THE VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO. 6 PELLETS

Rheogram		As-Received Moisture, %	Slurry Properties										Thixotrop- ic/ Rheoplectic	
			No.	Descrip- tion	Coal, % Weight %	A-23 % of Coal	Flocon % of Coal	Slurry, °C		Viscosity, Centipoise		Rheology ^b		
								Start	End	100 s ⁻¹	500 s ⁻¹			1,000 s ⁻¹
Lignin Sulfonate Spheres														
	I-18	Air Dried	3.35	54.6	0.73	None	19.8	19.8	540	340	320	Pseudo-Plastic	Neither	
	I-19	Air Dried	3.35	54.6	0.73	None	43	44	290	200	190	Pseudo-Plastic	Neither	
	I-20	Air Dried	3.35	54.6	0.73	None	60	50	175	135	135	Pseudo-Plastic	Thixotropic	
	I-21	Oven Dried	3.36	54.6	0.67	None	22.5	24	475	290	270	Pseudo-Plastic	Neither	
	I-22	Oven Dried	3.36	54.6	0.67	None	43	42	250	170	160	Pseudo-Plastic	Thixotropic	
	I-23	Oven Dried	3.36	54.6	0.67	None	63	58.5	200	120	115	Pseudo-Plastic	Thixotropic	
Shur Bond Spheres														
	I-24	Air Dried	7.45	54.8	0.75	None	21	23	500	380	378	Pseudo-Plastic	Neither	
	I-25	Air Dried	7.45	54.8	0.75	None	43	42.5	220	180	195	Near-Newtonian	Thixotropic	
	I-26	Air Dried	7.45	54.8	0.75	None	62	58.5	150	115	125	Near-Newtonian	Thixotropic	
	I-27	Oven Dried	17.00	54.9	0.97	None	22.5	23.5	510	430	445	Near-Newtonian	Neither	
	I-28	Oven Dried	17.00	54.9	0.97	None	42	41	210	190	210	Near-Newtonian	Thixotropic	
	I-29	Oven Dried	17.00	54.9	0.97	None	62	59	150	155	140	Near-Newtonian	Thixotropic	
Starch Spheres														
	I-30	Air Dried	3.39	54.4	1.02	None	23	24	510	470	450	Near-Newtonian	Thixotropic	
	I-31	Air Dried	3.39	54.4	1.02	None	42	43	225	240	260	Near-Newtonian	Thixotropic	
	I-32	Air Dried	3.39	54.4	1.02	None	63	59.5	175	150	160	Near-Newtonian	Thixotropic	
	I-33	Oven Dried	3.46	54.2	1.39	None	21.5	22	485	460	455	Near-Newtonian	Thixotropic	
	I-34	Oven Dried	3.46	54.2	1.39	None	43	42	200	235	255	Near-Newtonian	Thixotropic	
	I-35	Oven Dried	3.46	54.2	1.39	None	63	59.5	100	130	135	Near-Newtonian	Thixotropic	

^a Including binder.

^b Dilatant if indicated viscosity at 1,000 s⁻¹ is more than 1.5 times indicated viscosity at 100 s⁻¹. Near-Newtonian if indicated viscosity at 1,000 s⁻¹ is between 0.8 and 1.5 times viscosity at 100 s⁻¹. Pseudo-Plastic if indicated viscosity at 1,000 s⁻¹ is less than 0.8 times viscosity at 100 s⁻¹.

Figures 3 through 5 are plots of the relative viscosity versus temperature of the slurries from pellets containing the three types of binders. There did not appear to be any substantial difference in behavior between slurries prepared from the oven-dried and air-dried pellets, so results for the two types of pellets are plotted together in these figures. Figures 6 through 8 show the same data after the relative viscosities were normalized to a constant 53.6 volume percent (54.6 weight percent at 20 C) loading to compensate for the small differences in the initial compositions of the slurries and for the greater expansion of water than coal when the slurries were heated. (The viscosity of slurries such as these is very sensitive to loading, so the Dougherty-Krieger equation, Reference 1, was used for the normalization.) The lines plotted in Figures 6 through 8 were from a least square regression of the combined set of normalized data. The slurries prepared from the pellets with lignin sulfonate binder were shear-thinning, while slurries prepared from pellets containing the other two binders were near-newtonian over the shear rate range of 100 to 1,000 sec^{-1} .

The temperature coefficients of the normalized slurry viscosity were also different for the three binders:

Binder	A-23, %	Computed Viscosity, cP 20 C, 100 s^{-1}	Relative Viscosity Coefficient, $(^\circ\text{C})^{-1}$
Lignin Sulfonate	0.7	501	-2.0
Shur Bond	0.7 - 1.0	466	-3.8
Corn Starch	1.0 - 1.4	589	-5.3

The negative relative viscosity coefficients suggest that the effectiveness of the A-23 dispersant improves with increasing temperatures. Positive coefficients have been reported for some types of dispersants.

FIGURE 3. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM ILLINOIS No.6 PELLETS CONTAINING LIGNIN SULFONATE BINDER

FIGURE 4. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM ILLINOIS No.6 PELLETS CONTAINING SHUR BOND BINDER

FIGURE 5. CHANGE IN RELATIVE VISCOSITY WHEN HEATING SLURRY PREPARED FROM ILLINOIS No.6 PELLETS CONTAINING CORN STARCH BINDER

FIGURE 6. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING LIGNIN SULFONATE BINDER

FIGURE 7. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING SHUR BOND BINDER

FIGURE 8. EFFECT OF TEMPERATURE IN NORMALIZED RELATIVE VISCOSITY OF SLURRY PREPARED FROM PELLETS CONTAINING CORN STARCH BINDER

Mixing Techniques. Alternative methods for disintegrating the pellets were investigated which might offer advantages over the stirred ball mill procedure followed for the amenability testing. The alternative devices were all stirrers with various types of blades. None was quite as effective as the stirred ball mill for breaking up the fragments of pellets when reslurrying the pellets. The following are comparison results for the different types tested on 600-gram lots of slurry:

Device	rpm	Mix Time, Minutes	+48 Mesh Remaining, Dry Weight %
Typical Stirred Ball Mill		3	None
Double Opposed Ship Prop	1,200	5	20.5
Flat Serrated-Edge Type 1	1,200	5	16.1
Flat Serrated-Edge Type 2	1,200	5	17.8
Flat Serrated-Edge Type 3	2,500	3	2.8
Flat Serrated-Edge Type 3	2,500	12	1.2
Shrouded Flotation Prop	1,200	5	4.9

It appears that the flat serrated-edge type blade, such as commonly used with a Cowles Dissolver, is quite effective provided it rotates at a sufficient speed. These blades are designed to provide an intense shearing action to viscous materials. The laboratory froth flotation machine type mechanism also performed quite well. Flotation mechanisms have a pumping action where the slurry is forced through restricted channels, which also provide an intense shearing action.

Presoaking, preheating, and ultrasonic conditioning were also investigated as methods to assist the disintegration of the pellets, but none of the treatments seemed to speed the disintegration to any great extent.

It appears to be very difficult to eliminate the last few pellet fragments by stirring a highly loaded slurry. A gear pump was procured and tested as one method for crushing these residual fragments before the slurry is atomized (see discussion on page 16).

Reslurrying Filter Cake and Pellets. Bench tests were made to reslurry Illinois No. 6 filter cake and pellets of Illinois No. 6 with a corn starch binder and pellets of Upper Elkhorn with a Shur Bond binder. The slurrying was done on pre-crushed pellets using a ship-prop mixer. The ship-prop mixer did not break up the corn starch pellets adequately, so that slurry was mixed for an additional period with a high-speed flat blade to disintegrate the remaining lumps. The final slurries were essentially minus 48 mesh (300 μ m). A-23 dispersant was added in small increments during each of the reslurrying experiments to reduce the viscosity of the mixtures and achieve the target viscosity of approximately 500 cP. The composition and viscosity data shown in Table 2 were obtained from these tests.

TABLE 2. BENCH SLURRY PREPARATION TESTS

	Illinois No. 6 Filter Cake	Illinois No. 6 Starch Bonded Pellets	Upper Elk- horn Shur-Bond Bonded Pellets
Coal (with binder), Weight %	52.33	55.81	55.93
Water, Weight %	46.36	43.77	44.00
A-23, Weight % of Dry Coal	2.51	0.75	0.12
Mixing Time, Minutes	10	45	10
Viscosity, cP			
at 100 s ⁻¹	575	625	525
at 500 s ⁻¹	815	330	385
at 1,000 s ⁻¹	815	285	350

Particle size distributions for the original clean coals and for the reslurried products listed in Table 2 are given in Tables 3 and 4. There appears to be a significantly larger fraction of minus 1-micrometer material

TABLE 3. PARTICLE SIZE DISTRIBUTIONS OF RESLURRIED FILTER CAKE
AND PELLETS PREPARED FROM ULTRA-FINE ILLINOIS No. 6 COAL

	Dry Weight Passing, %		
	Original Clean Coal	Reslurried Material	
		Filter Cake	Corn Starch Pellets
Particle Size Passing, μm			
300		99.72	99.58
75	99.90	99.53	98.58
38	99.07	94.60	
30	94.98	84.13	98.58
20	92.57	74.92	86.05
15	74.98	69.12	78.18
10	53.35	57.55	67.68
8	42.09	52.17	60.37
6	28.47	42.80	51.89
4	14.91	29.64	38.92
2	3.37	14.23	20.97
1	0.59	5.48	9.08
MMD, μm	11.4	14.4	11.7

TABLE 4. PARTICLE SIZE DISTRIBUTIONS OF RESLURRIED
PELLETS PREPARED FROM ULTRA-FINE UPPER ELKHORN COAL

	Dry Weight Passing, %	
	Original Clean Coal	Reslurried Shur Bond Pellets
Particle Size Passing, μm		
300	99.88	99.99
75	99.32	99.18
38	97.93	92.64
30	96.03	88.02
20	87.99	75.82
15	76.37	68.15
10	62.91	60.49
8	54.24	49.81
6	43.35	40.37
4	29.80	36.03
2	12.20	20.24
1	3.06	9.96
MMD, μm	10.7	13.1

in the reslurried products than in the original clean coals. It is not clear at this time whether this increase represents a fine binder added during pelletization, comminution which may have occurred during the various dewatering/pelletizing/reslurrying steps, or the dispersion of natural agglomerates remaining from the coal cleaning process. In any event, the additional amount of fines provides a more bimodal particle size distribution which seems to improve the rheology of the slurries.

The practicality of using a Viking gear pump to break up the lumps in a slurry was also investigated. A gear pump was considered because it applies a squeezing action to the slurry much like a roll crusher would. Two tests were made. In the first, the pellets were slurried for 1 minute with a high-speed mixer and the slurry passed through the pump one time. The resulting slurry still contained 10.2 percent (dry basis) plus 48-mesh (300-micrometer) lumps. The slurry was then passed through the pump two more times, and the amount of plus 48-mesh lumps was reduced to 5.5 percent. In the second test, the high-speed mixing continued for 15 minutes and the resulting slurry was passed through the gear pump three times. The 15 minutes of high-speed mixing reduced the amount of plus 48-mesh lumps to 2.8 percent. Very little reduction occurred during the pumping steps since the final slurry still contained 2.1 percent lumps. It appears from these tests that a gear pump may have a place for controlling the top size of solids in slurries by crushing the larger lumps, but the smaller lumps, those approaching 300 μm in diameter, will not be broken. (As will be noted later in the section on atomization testing, the slurry after passing through a progressive cavity pump and strainer, as used in the University of Alabama atomization tests, effectively remove this small quantity of pellet fragments.)

Effects of Dilution, Aging, and Dispersant Dosages. A brief investigation was made to determine the effect of small differences in slurry dilution and A-23 additions on viscosity. Slurry samples remaining from the temperature variation studies conducted earlier were used for this work. These slurries were made from pelletized Illinois No. 6 clean coal. For the first part of the investigation, small amounts of dilution water were added to the original slurry samples, and the viscosities were measured after each incremental dilution. Three or four water additions were made to each

sample so that a set of viscosity measurements was obtained for samples containing between 52.8 and 54.8 percent by weight of the same dispersed particulate material. The dilution/viscosity data are listed in Table 5. As expected from previous work¹, the viscosities at the three shear rates checked (at 100, 500, and 1,000 sec^{-1}) show a linear relationship when plotted on a logarithmic scale against total solids or particulate solids concentration. This is illustrated in Figures 9 and 10. Judging from the plotted data, one can expect a 30 to 60 percent reduction in slurry viscosity when one reduces the solids loading of a slurry by 1 percent.

The above viscosity measurements also provide an indication of the effect that aging has upon slurry rheology since the original samples had been stored for about one month before starting the dilution studies. The viscosity measurements made before and after storage are compared in Table 6. In each instance, there was a considerable rise in viscosity during storage, although the increase was most pronounced at the 100 reciprocal second shear rate.

A freshly prepared slurry was used to determine the effect of changing dispersant concentration upon rheology. The slurry was prepared by grinding air-dried pellets containing a corn starch binder in a stirred ball mill with the proper amount of A-23 based upon previous testing. Viscosity measurements were made before and after small increments of A-23 were added to this slurry. The data are presented in Table 7 and plotted in Figure 11. As shown in this figure, a 30 percent increase in the amount of A-23 added cut the viscosity at 100 sec^{-1} by more than half. The extra A-23 also changed the rheology from a pseudoplastic shear-thinning behavior to a dilatant shear-thickening behavior. Similar A-23 addition tests are planned for slurries prepared from pellets containing Shur Bond and lignin sulfonate binders.

TABLE 5. RESULTS OF DILUTION TESTS ON RESLURRIED ILLINOIS
NO. 6 SPHERES (ORIGINAL SLURRIES STORED FOR ABOUT 1 MONTH)

Slurry Total Solids, %	Viscosity, Centipoise			Dispersant (A-23), %	Coal, Weight %
	100 s ⁻¹	500 s ⁻¹	1,000 s ⁻¹		
Air-Dried with Lignin Sulfonate Binder					
55.02	1,150	475	420	0.73	54.62
54.33	725	360	310	0.73	53.94
54.15	550	285	250	0.73	53.76
53.60	350	210	190	0.73	53.21
Oven-Dried with Shur Bond Binder					
55.41	1,495	760	655	0.97	54.88
54.93	1,000	555	495	0.97	54.40
54.12	525	315	290	0.97	53.60
53.66	400	240	220	0.97	53.14
Air-Dried with Corn Starch Binder					
55.05	2,050	695	550	1.02	54.49
54.56	1,200	540	450	1.02	54.01
54.04	800	425	360	1.02	53.49
53.58	625	360	315	1.02	53.04
53.28	450	290	260	1.02	52.74
Oven-Dried with Corn Starch Binder					
55.23	1,350	675	570	1.53	54.40
54.67	825	500	440	1.53	53.85
54.21	575	395	350	1.53	53.39
53.81	425	320	295	1.53	53.00

FIGURE 9. EFFECT OF SMALL DILUTIONS ON THE VISCOSITY OF SLURRIES PREPARED FROM AIR DRIED AND OVEN-DRIED ILLINOIS NO.6 PELLETS PREPARED WITH A CORN STARCH BINDER

FIGURE 10. EFFECT OF SMALL DILUTIONS ON THE VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO.6 PELLETS PREPARED WITH A LIGNIN SULFONATE AND SHUR BOND BINDERS

FIGURE 11. EFFECT OF INCREASED DISPERSANT DOSAGE ON VISCOSITY OF SLURRIES PREPARED FROM ILLINOIS NO.6 PELLETS CONTAINING CORN STARCH BINDER

TABLE 6. COMPARISONS OF SLURRY VISCOSITIES
BEFORE AND AFTER ONE-MONTH STORAGE

Slurry Total Solids, %		Viscosity, Centipoise			A-23, %	Coal, Weight %
		100 s ⁻¹	500 s ⁻¹	1,000 s ⁻¹		
Air-Dried with Lignin Sulfonate Binder						
Before	55.00	540	340	320	0.73	54.60
After	55.02	1,150	475	420	0.73	54.62
Oven-Dried with Shur Bond Binder						
Before	55.45	510	430	445	0.97	54.92
After	55.41	1,495	760	655	0.97	54.88
Air-Dried with Corn Starch Binder						
Before	55.00	510	470	450	1.02	54.44
After	55.05	2,050	695	550	1.02	54.49
Oven-Dried with Corn Starch Binder						
Before	55.00	485	460	455	1.53	54.17
After	55.23	1,350	675	570	1.53	54.40

TABLE 7. EFFECT OF INCREMENTAL A-23 ADDITIONS ON THE VISCOSITY OF FRESH
SLURRY PREPARED FROM AIR-DRIED PELLETS CONTAINING CORN STARCH BINDER

Slurry Total Solids, %		Viscosity, Centipoise			Total A-23, %	Coal, Weight %
		100 s ⁻¹	500 s ⁻¹	1,000 s ⁻¹		
As Prepared	55.71	1,200	675	580	1.01	55.15
Diluted	55.00	700	470	420	1.01	54.45
Added A-23	54.99	525	450	420	1.07	54.41
Added A-23	54.97	290	345	360	1.19	54.32
Added A-23	54.95	250	315	340	1.31	54.24

Slurry Atomization

A series of slurry atomization tests were conducted on 200-lb samples of the following three samples:

- Illinois No. 6 coal, starch-bound disk pellets
- Illinois No. 6 clean-coal filter cake
- Elkhorn, Shur Bond-bound, disk pellets.

The pellets were prepared at Battelle in late June, 1991 and shipped to Jim Walter Resources in Brookwood, AL for testing by the University of Alabama (UA). Details of the Test program and results are provided in the UA report included as Appendix C.

In brief summary, the coal pellets (pre-ground to -20 mesh at Battelle before shipping) were mixed with water, dispersant (A-23) and agitated in an open top 55-gal drum. A simple three prop propeller was used to successfully convert the coal into CWF, see Figures 12 and 13. No stabilizer was used or needed. The slurry showed good uniformity and short-term stability, viscosities generally below 500 cP @100 sec⁻¹, and a shear thinning behavior up to the maximum shear rate measured (1000 sec⁻¹). The slurry was pumped by a moyno progressive cavity pump into the atomization test chamber. Any particles not thoroughly disintegrated during the formulation stage were reduced to -325 mesh by passage through the pump and the strainer placed before the nozzle. The slurry was atomized during short test periods at flow rates of approximately 128 lb slurry/hr, see Figures 14 and 15. The slurry droplet size was measured by a Malvern 2600 laser-based particle size counter. The test data were automatically manipulated by the Malvern to generate particle-size distributions in terms of Sauter Mean Diameter (SMD). The particle SMD data for the three coals, at an air to fuel (A/F) ratio of 1.12 to 1.20, show:

- Illinois No. 6 coal pellets: 35 μm
- Illinois No. 6 filter cake: 68 μm
- Elkhorn pellets: 38 μm .

Data at other A/F ratio are provide in Appendix C. The Elkhorn coal slurry atomized the best of the three coals. Also, it was found that the required quantity of A-23 dispersant was significantly lower than the optimal dosage levels found in the lab-scale tests.

FIGURE 12. COAL PELLETS BEING CONVERTED INTO CWF

FIGURE 13. SIMPLE 3 PROP PROPELLER USED FOR SLURRY FORMULATION

FIGURE 14. SLURRY ATOMIZATION TEST CHAMBER

FIGURE 15. CLOSEUP OF ATOMIZED ILLINOIS No. 6 PELLET SLURRY

The results show that strong, durable (and in the case of Shur Bond binder waterproof) pellets can be readily formulated into a low viscosity, stable, atomizable slurry with low SMD droplet sizes. The pellets actually required up to 30 percent less dispersant to make an equal quality slurry and produced droplets with a smaller average size compared to the filter cake.

Selected Processes for Task 3 Evaluation

Based on the coal reconstitution, slurry formulation, and atomization testing the following processes and binders have been selected for larger scale, pilot plant testing:

Selected Reconstitution Processes

- Elkhorn: Roller-and-Die Pelletization and Disk Pelletizing
- Illinois No. 6: Roller-and-Die Pelletization and Disk Pelletizing
- Utah: Roller-and-Die Pelletization and Extrusion Pelletization.

Selected Binders

- Pre-gelatinized corn starch
- Shur Bond.

Limited testing of calcium lignin sulfonate binder is also planned.

Tasks 3 through 7

No work was scheduled or initiated on these tasks in the fourth quarter.

Task 8 - Utilization/Commercialization

Although work on this task was not originally scheduled to begin until February of 1992, it became necessary to begin this work early in order to make appropriate selections of the preferred reconstitution techniques for each coal. Based on the findings of the large-scale coal slurry atomization studies, the originally estimated cost for slurry preparation are too high. Cost for formulation equipment, dispersant and stabilizer chemical costs can be reduced. The drop in overall coal filter cake-to pellets-to slurry costs

could be as large as \$5 to \$10/ton. This effect will be quantified in future Task 8 efforts to estimate overall system costs.

Task 9 - Prepare Additional Cake

Work on Task 9 was continued this quarter. Cleaned Illinois No. 6 and Utah coal filter cake were prepared by AMAX. The Illinois No. 6 coal was delivered to Battelle, and the Utah coal has been prepared and is ready for shipment at Battelle's direction. The coal was received, pre-ground through a crusher, a ball mill, and then reduced to final micronized size using a 40-liter Draiswerke stirred ball mill. The slurry was diluted to 2 to 3 percent solids, mixed with diesel fuel collector and MIBC frother and fed to two banks in series of conventional pilot-scale flotation cells. The clean coal was filtered in an Eimco filter press. The cleaning equipment is similar to that described in the 2nd Quarterly Report describing the Illinois No. 6 cleaning activities.

About 3,400 lbs (2,000 lbs dry equivalent) of the Illinois No. 6 and 3,300 lbs (2,050 dry equivalent) of the Skyline Mine Utah clean-coal filter cake were prepared. Moisture and ash analyses of the two clean-coal filter cakes are shown in Table 8. The values are very similar to the original 1,000 lb lots provided for Task 1 and 2.

TABLE 8. ANALYSIS OF CLEANED ILLINOIS AND UTAH COAL

Characteristic	Illinois No. 6	Utah
Moisture, %	42.5	37.9
Ash, %	4.38	2.58

The cleaned coals were analyzed for ultimate and proximate analysis, ash fusion temperatures, sulfur forms, mineral analysis, oxidation index, and particle size distribution. Chemical analyses and particle size distributions of the Illinois No. 6 clean coal is included in Appendix D. (The Utah analysis is not available at this time, but should be available to include in the Final version of this quarterly report.)

The originally planned scope of Task 9 included the production of 2,000 lbs (dry equivalent) of Illinois No. 6 and Utah coals -- 1,000 lbs for small-scale testing and 1,000 lb for pilot scale testing. This effort has been completed. However, it is desirable to have more than the planned 1,000 lbs of each clean coal for the large-scale storage, handling, and transportation tests. Therefore, since the Task 9 effort was (and still is) under budget, this effort was extended to provide an extra 2,000 lb (dry equivalent) of both Illinois No. 6 and Utah coals. This material was produced during this quarter.

In addition, 4,000 lb (dry equivalent) of cleaned Elkhorn coals is needed for the pilot plant tests. The original 1,000 lb sample of Elkhorn coal was supplied by Virginia Poly Tech, rather than AMAX, due to their short lead time for production. AMAX can provide the needed clean Elkhorn coal with their equipment. With U. S. DOE's approval we plan to authorize AMAX to supply 4,000 lb (dry equivalent) of Elkhorn clean-coal filter cake for testing.

PLANNED FUTURE ACTIVITIES

Work in the fifth quarter was scheduled to only involve Task 3. However, it is now anticipated that work on Tasks 4 (Evaluate Storage Characteristics), 5 (Evaluate Handling Characteristics), 6 (Evaluate Transportation Characteristics), 7 (Reslurry Pellets and Evaluate CWF), and 8 (Utilization/Commercialization) will be initiated early. Also, if we plan to acquire more clean coal, extending the Task 9 (Prepare Additional Cake) activities.

In Task 3 work will focus on the large scale production of pellets. Efforts will include large scale pelletization and pellet/slurry quality evaluation. We plan to:

- Evaluate Shur Bond and corn-starch pellets for all three coals with the two processes recommended.
- Select one coal and one pelletization process and study the lignin sulfonate binder.
- Conduct large scale production tests, see Table 9. 900 lbs of pellets are required for each coal/binder combination.
- Test pellet properties of one pellet from each coal against its raw parent coal in an actual truck transportation tests. The

estimated pellet quantity required for a 55 gallon drum filled to 1/2 - 3/4 its capacity is ~ 200 lbs.

- Select for each coal, one pellet/binder combination for "super-pellet" production. The "super-pellet" would contain all the additives that are necessary including reslurrying. The aim of making this type of pellet would be to ensure that at the user site only minimal effort will be required for the reslurrying process, i.e., crushing and adding water. The estimated quantity required for the "super-pellet" study is 500 lbs.
- The total quantity of pellets required for each coal in the Task study is:

(1) For 2 processes X 2 binders @ 1000 lbs each:	4000 lbs
(2) For lignin sulfonate binder study :	1000 lbs
(any one of the coal)	
(3) For truck transportation simulation	
(1 X 200):	200 lbs
(4) For "super-pellet" study (1 X 500) :	500 lbs
Total:	<u>5700 lbs</u>
at 40 percent moisture	
Filter cake required:	~7980 lbs
	<u>~8000 lbs</u>

TABLE 9: PHASE II TEST PLAN

	Type of Test	Quantity of Pellets (lbs)	Test Description/Remarks	Purpose
1	Vibration	100	<ul style="list-style-type: none"> - Test module needs to be built. Draft design is attached (Figure ??) - Set a reference data base with Utah/Wyoming raw coal - Quantify the fines generated from pellets and its raw coal 	Simulation of handling and transportation characteristics
2	Humidity	50	<ul style="list-style-type: none"> - 5 tests for each coal/binder combination - Humidity controlled chamber availability at Battelle 	Simulation of transportation and storage characteristics
3	Heat-cycle	15	<ul style="list-style-type: none"> - Test for the temperature of spontaneous combustion 	Simulation of transportation and storage characteristics
4	Outdoor Storage	400	<ul style="list-style-type: none"> - Sample 8 lbs after 1,2,4,12, and 25 week - Evaluate pellet strength and slurry quality 	Storage Characteristics
5	Packing	150	<ul style="list-style-type: none"> - 3 bags made of various types of materials - 50 lbs of pellets required for each bag 	Storage evaluation
6	Pellet uniformity	15	<ul style="list-style-type: none"> - Sample 3 lbs of pellets from every 150 lbs of pellet production - Check for strength, durability, weatherability, and other routine data 	Pellet quality evaluation
7	Slurry uniformity	25	<ul style="list-style-type: none"> - Sample 5 lbs of pellets from every 150 lbs of pellet production - Check for consistency of slurry preparation in terms of dosage, viscosity, etc. - Only simplified reslurrying procedure needs to be adopted 	Evaluation of slurry quality
8	Slurry Production	150	<ul style="list-style-type: none"> - 250 to 300 lbs slurry production - Production to be carried out using a continuous reslurrying circuit. - Reslurrying circuit to be put together. 	Evaluation of slurry quality

SUMMARY

Significant accomplishments were made during the fourth quarter: they include:

- Preferred reconstitution processes and binders were selected for pilot plant study with each of the three coals: roll-and-die and disk pelletization were selected for Elkhorn and Illinois No. 6 coals, and roller-and-die and extrusion pelletization for the Utah coal; preferred binders: pre-gelatinized corn starch and Shur Bond
- Slurry formulation tests show simple mixing techniques (less expensive than the stirred ball mill technique assumed in the preliminary cost evaluation) can be used to prepare quality slurries
- Large scale atomization tests indicate that the clean-coal pellets can be readily converted into slurry and atomized into fine droplet sizes
- Slurry formulation results indicate that initial estimates of coal-to-slurry costs are too high, overall costs may be reduced \$5 to \$10/ton
- About 4,000 lb of froth-flotation cleaned Illinois No. 6 and Utah coal filter cake (2,000 and 2,050 lbs dry basis, respectively) were prepared for the pilot-scale reconstitution and slurry production testing
- The project is on schedule and slightly below budget.

APPENDIX A

RECONSTITUTION DATA BASE

APPENDIX A

RECONSTITUTION DATA BASE

Presented below in Tables A-1 through A-9 are the complete reconstitution data base for the three coals and the various binders considered.

TABLE A-1. ELKHORN COAL ROLLER-AND-DIE PELLETIZATION DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test Pass (P)/ Fail (F)		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							1 ft	5 ft			
Methocel	DOW-F4M	1	26	NA	217	76	P	P	77	95	84
	DOW-A4M	1	26	73	369	101	P	P	97	99	92
Corn Starch	Allbond 200	1	26	NA	80	31	P	F	57	91	0
		3	26	NA	129	76	P	P	63	94	67
Lignosulfonate		5	26	NA	242	133	P	F	95	99	92
		1	26	NA	44	0	P	F	36	74	0
Soya Residue		3	26	NA	55	0	P	F	40	80	0
		5	26	NA	73	0	P	F	60	89	0
Asphalt Emulsion		1	26	NA	72	50	P	F	13	61	20
		3	26	NA	74	58	P	P/F	26	76	94
HR-2718		5	26	NA	53	75	P	P	36	79	85
		1	26	NA	47	51	P	F	28	58	80
HR-2719		3	26	NA	42	45	P	P/F	34	67	88
		5	26	NA	26	31	P	P	22	68	87
HR-2719		1	26	80	53	76	P	P/F	15	64	73
		3	26	67	76	44	P	P/F	19	76	95
HR-2719		5	26	73	26	42	P	P/F	7	51	93
		1	26	49	75	0	P	P/F	26	80	2
A-23		2	26	52	128	0	P	P	35	93	13
		5	26	NA	46	33	P	P/F	8	65	0
Pitch		1%/300	26	67	114	0	P	P/F	29	86	2
		2%/0.07	26	70	242	0	P	P	43	90	2
Dispersant and Stabilizer	A-23, Flocon 4800 C	2%/0.07/1%	26	66	440	85	P	P	77	96	57
	A-23, Flocon 4800 C, Allbond 200										
Shur-Bond (7:1 dilution)	Sherax Chem.	3%	26	56	57	51	P	P/F		57	

TABLE A-2. ELKHORN COAL DISK PELLETING DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							Pass (P)/ Fail (F)				
							1 ft	5 ft			
Corn Starch	Allbond 200	3	38	21.7	421	82	P	P	78	96	13
Dispersant	A-23	1	38	47	35	0	P	P/F	4	25	0
Lignin Sul- fonate		5	38	136	319	134	P	P	71	99	0

TABLE A-3. ELKORN COAL EXTRUSION PELLETIZATION DATA

[illegible]

TABLE A-4. ILLINOIS NO. 6 COAL ROLLER-AND-DIE PELLETIZATION DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weatherin dex (WI)
							Pass 1 ft	Fail (F) 5 ft			
Corn Starch	Ailbond 200	3	27	165	410	126	P	P/F	76	96	59
Ligninsulfonate		3	27	70	124	0	P	P/F	37	83	0
Asphalt Emulsion	HR-2719	1	27	88	86	49	P	P/F	22	70	0
Dispersant	A-23	1	26	80	95	0	P	P/F	32	79	0
Corn Starch and ligninsulfonate		1%/1%	26	75	156	24	P	P/F	43	85	0

TABLE A-5. ILLINOIS NO. 6 COAL DISK PELLETTING DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							Pass (P)/ 1 ft	Fail (F) 5 ft			
Corn Starch	Allbond 200	3	38	109	509	31	P	P	92	99	7
Dispersant	A-23	1	38	72	84	0	P	P/F	19	84	0
Lignin Sulfonate		3	38	99	225	0	P	P	54	98	0
Asphalt Emulsion	HR-2719	1	38	45	38	0	P	P/F	7	49	0
Corn Starch & Lignin Sulfonate		1%/1%	38	74	128	0	P	P	64	96	0

TABLE A-6. ILLINOIS NO. 6 COAL EXTRUSION PELLETIZATION DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							Pass (P)/ Fail (F)				
							1 ft	5 ft			
Corn Starch	Allbond 200	3	40	43	151	32	P	P/F	53	94	44
Asphalt & Corn Starch	2719 & Allbond 200	2/1.5	40	29	67	36	P	P	40	86	NA
Shur Bond & Corn Starch	- & Allbond 200	3/1.5	40	39	31	30	P	P	59	92	NA

NA: Data not available.

TABLE A-7. UTAH COAL ROLLER-AND-DIE PELLETTIZATION DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							Pass (P)/ Fail (F)	5 ft			
Corn Starch	Allbond 200	3	32	118	199	108	P	P/F	68	93	36
Dispersant	A-23	1	32	53	62	28	P	P/F	21	67	0
Lignin Sulfonate		3	32	65	96	37	P	P/F	46	83	7
Asphalt Emulsion	HR-2719	1	32	NA	59	36	NA	NA	31	81	19
Corn Starch & Lignin Sulfonate		1%/1%	32	72	97	56	P	P/F	32	83	23

TABLE A-8. UTAH COAL DISK PELLETING DATA

Binder	Designation	Conc. wt. %	Process Moisture %	Green Strength lbs/in ³	Set Strength lbs/in ³	Wet Strength lbs/in ³	Drop Test		Durability Index (DI)	Ro-Tap Durability Index (RDI)	Weather. Index (WI)
							Pass (P)/ 1 ft	Fail (F) 5 ft			
Corn Starch	Allbond 200	3	38	102	183	105	P	P	88	97	24
Dispersant	A-23	1	38	68	45	0	P	P	63	72	0
Lignin Sulfonate		3	38	121	74	0	P	P/F	46	95	0
Asphalt Emulsion	HR-2719	1	38	NA	49	0	NA	NA	41	66	0
Corn Starch & Lignin Sulfonate		1%/1%	38	88	102	0	P	P	61	94	0

APPENDIX B

SLURRY FORMULATION DATA BASE

APPENDIX BSLURRY FORMULATION DATA BASE

Presented below in Tables B-1 through B-9 are the complete slurry formulation data base for the three coals and the CWF additives being considered.

TABLE B-2. ELKHORN COAL DISK PELLETS - CWF DATA

Binder	Designation	Conc. wt. %	As Recd Moisture %	Slurry Properties			Viscosity, cp			Stability
				Coal wt. %	A-23 % of Coal	Flocon % of Coal	at 100 sec ⁻¹	at 500 sec ⁻¹	at 1000 sec ⁻¹	
Corn Starch	AllBond 200	3	1.81	55.4	0.11	None	525	415	400	Very good
Dispersant	A-23	1	1.92	56.7	0.26	0.02	510	770	870	Very good
Lignin Sulfonate		5	1.82	56.5	0.44	None	525	340	335	Very good
No Binder		0	27.04	54.5	0.90	0.08	200	370	385	Very good

TABLE B-6. ILLINOIS NO. 6 COAL EXTRUSION PELLETS CWF DATA

[illegible]

TABLE B-7. UTAH COAL ROLLER-AND-PIE-PELLET CWF DATA

Binder	Designation	Conc. wt. %	As Recd Moisture %	Slurry Properties			Viscosity, cp			Stability
				Coal wt. %	A-23 • % of Coal	Floccn % of Coal	at 100 sec ⁻¹	at 500 sec ⁻¹	at 1000 sec ⁻¹	
Corn Starch	AllBond 200	3	27.07	53	3.66	0.03	500	530	560	Very good
Lignin Sulfonate		3	29.70	54	1.81	0.04	560	490	490	Very good
Asphalt Emulsion	HR-2719	1	29.10	54.1	1.63	None	500	555	570	Very good
Dispersant	A-23	1	26.70	54.1	1.67	None	540	625	660	Very good
Corn Starch & Lignin Sul.		1 & 1	27.63	53.8	2.16	None	525	590	620	Very good

TABLE B-9. UTAH COAL EXTRUSION PELLET-CWF DATA

Binder	Designation	Conc. wt. %	As Recd Moisture %	Slurry Properties			Viscosity, cp			Stability
				Coal wt. %	A-23 % of Coal	Flocon % of Coal	at 100 sec ⁻¹	at 500 sec ⁻¹	at 1000 sec ⁻¹	
Corn Starch	AlIBond 200	3	5.55	53.6	2.58	None	525	670	660	Very good
Asphalt Emulsion & Corn Starch	HR-2719 & AlIBond 200	2 & 1	2.86	54.2	2.86	0.14	450	555	665	Very good
Shur Bond & Corn Starch		3 & 2	4.52	54	1.67	None	500	805	820	Marginal
Lignin & Corn Starch		3 & 2	5.75	53.7	2.41	None	525	830	800	Good

APPENDIX C

ATOMIZATION OF THREE BATTELLE COAL-WATER FUELS

APPENDIX C

ATOMIZATION OF THREE BATTELLE COAL-WATER FUEL

Attached is a copy of the report prepared by Dr. David W. Arnold of the University of Alabama on the slurry formulation and atomization tests he conducted with Battelle and AMAX representatives at Jim Walters Resources. A discussion of the test and the positive results obtained was presented in the body of this report.

CHEMICAL ENGINEERING

THE UNIVERSITY OF ALABAMA
College of Engineering

July 17, 1991

Jembu K. Raghavan, Ph.D.
Process Engineering Dept.
Battelle
505 King Avenue
Columbus, OH 43201-2693

Dear Jembu:

Enclosed is the report entitled "Atomization of Three Battelle Coal-Water Fuels". If you need them, I can send rheograms of the Elkhorn CWF. It proved impossible to adjust the viscosity of a batch of CWF in the mix tank at the atomization unit in less than 3 hours to the desired value of 500 centipoise. In future work we can develop a formula that gives the same viscosities for the CWF's before we go to the atomization unit.

I look forward to further work with you.

Sincerely,

David W. Arnold
Associate Professor

DWA/gk
Battelle.ltr

cc: Bruce Hamilton
Jeff Armstrong

Atomization of Three Battelle Coal-Water Fuels

On Tuesday, July 2, 1991 Bruce Hamilton and Jeff Powell of Jim Walter Resources, Inc. (JWRI) formulated a coal-water fuel (CWF) from the material contained in the drum labeled Illinois #6 filter cake with corn starch. All of the CWF formulation work was done at the JWRI Training Center in Brookwood, Alabama where the atomization spray test facility (ASTF) is located. In an attempt to make a CWF with a viscosity of 500 cp @ 100 sec⁻¹ solids and flocon were added to the slurry to thicken it. The weights of the coal from the drum, water, A-23 solution, and flocon are given in Table 1. The A-23 solution was 43 weight percent active ingredient and the flocon solution was added to bring the level of active ingredient to 400 PPM on a dry coal basis.

The CWF was mixed by first adding 36.2 kilograms of water, then adding 53.3 kilograms of the coal to the 55 gallon mixing drum, followed by 1180 grams of the A-23 solution. After agitation with the three-bladed impeller until no solids could be felt in the bottom of the mixing drum the viscosity was well below 500 cp @ 100 sec⁻¹. Adding 5.8 kilograms more coal and pumping from the mixing drum through a 20 mesh scale basket to the feed drum still did not produce a 500 cp slurry. Flocon was then added. Even though the viscosity was still not 500 cp, an atomization run was started because the CWF blending time had well exceeded the three hour limit.

Water was run first on the ASTF to verify operation of the ASTF. Then the Battelle CWF was pumped to the AGT nozzle without going through the 20 mesh scale basket. Small pieces of rubbery material caused some of the plugging problems, but other plugging appeared to be due to the nature of the CWF. After routing the CWF through the side of the duplex strainer with the screen, 15 "Malvern" readings were taken at 4 air to fuel ratio's (AFR). The feed rate was 128 PPH of CWF. The Sauter Mean Diameters (SMD) and obscuration are shown in Table 2. Above an obscuration of 0.5 a correction is needed for multiple scattering. Because most of the obscurations are below 0.5 or close to 0.5, no corrections are made to the SMD's for multiple scattering. The last four AFR's are probably the most reliable. The original "Malvern" plots for the largest and smallest droplets are included in the appendix. For the lowest AFR there are undoubtedly large drops beyond the detection limits of 564 microns.

In Table 3 are the apparent viscosities taken as the speed ramps up, holds for 3 minutes, and then ramps down. Sample 1 is the CWF from the feed drum before the atomization run, sample 2 is the CWF caught at the nozzle and run immediately, and sample 3 is the nozzle CWF run the next morning (Wednesday morning). In the appendix is the rheogram for sample 3. The maximum for the x-axis is 600 RPM or 1021 reciprocal seconds and the maximum for the y-axis is 4000 dyne. At 100 reciprocal seconds the apparent viscosity is 370 centipoise.

On Wednesday, July 3, 1991 the CWF from the Illinois #6 FC was run on the ASTF in much the same manner as the CWF run on the preceding day. The atomization runs are shown in chronological order and the very last AFR of 1.44 might be in error because of partial plugging. For the viscosities in Table 3, samples 1 and 2 are from the mix tank at 9:00 a.m. and 9:30 a.m. Samples 3 and 4 are from the nozzle at 11:30 a.m. and 2:00 p.m. during the atomization run. The rheogram for sample 2 is included in the appendix along with some original "Malvern" plots. At 100 reciprocal seconds the apparent viscosity is 260 centipoise.

On Friday, July 12, 1991 the run on the Elkhorn CWF was made. It atomized better than the Illinois #6 CWF's. However, it has an apparent viscosity of 252 centipoise at 100 reciprocal seconds, which is lower than the other CWF's.

Table 1. Formulation of Coal-Water Fuel (CWF)

Illinois #6 FC with Corn-Starch Binder on Tuesday, July 2, 1991.

	Kilograms
Coal (from drum, as received)	59.10
Water	36.28
A-23 Solution	1.100
Flocon	.179
Solids (Measured)	57.8 Weight Percent

Illinois #6 FC on Wednesday, July 3, 1991.

	Kilograms
Coal (from drum, as received)	78.56 (39.56% moisture)
Water	9.35
A-23 Solution	2.094
Solids (Measured)	50.8 Weight Percent

Elkhorn Coal on Friday, July 12, 1991.

	Kilograms
Coal (from drum, as received)	68.04 (23.0% Moisture)
Water	25.52
A-23 Solution	.341
Flocon	.175
Solids (Measured)	54.7 Weight Percent

Table 2. Sauter Mean Diameters and Obscurations for 3 CWF's
versus Air/Fuel Ratio

Illinois #6 FC with Corn-Starch Binder

AFR	SMD				Obscuration		
	Average	Std. Dev.	Coeff. Var.	# runs	Average	Std. Dev.	Coeff. Var.
.59	43.3	---	---	1	.641	---	---
1.44	28.5	---	---	1	.536	---	---
1.12	52.5	.4	.8	2	.396	.014	3.5
.86	48.4	---	---	1	.466	---	---
1.12	36.0	2.6	7.1	3	.516	.12	22.5
1.43	25.5	1.3	5.2	3	.564	.011	2.0
.88	65.5	8.0	12.2	2	.315	.005	1.8
.59	119.0	0	0	2	.185	.002	1.1

Illinois #6 FC

AFR	SMD				Obscuration		
	Average	Std. Dev.	Coeff. Var.	# runs	Average	Std. Dev.	Coeff. Var.
1.44	44.9	4.5	10.0	4	.349	.01	2.8
1.13	68.2	2.78	4.1	3	.23	.026	11.5
.89	109.0	12.6	11.6	4	.172	.016	9.5
.64	203.0	2.8	1.4	2	.104	.0068	6.5
1.44	77.8	4.3	5.5	---	.284	.016	5.7

Elkhorn Coal

AFR	SMD				Obscuration		
	Average	Std. Dev.	Coeff. Var.	# runs	Average	Std. Dev.	Coeff. Var.
.63	66.1	1.3	1.9	2	.352	.002	.5
.92	53.9	6.1	11.3	3	.406	.046	11.3
1.20	37.5	5.7	15.2	3	.487	---	.2
1.53	31.3	1.0	3.1	3	.558	.019	3.4

Illinois #6 FC with Corn-Starch Binder

Reciprocal Seconds	Sample 1		Sample 2		Sample 3	
	Up	Down	Up	Down	Up	Down
100	340	250	620	370	380	680
200	330	280	520	400	420	540
400	380	300	470	450	490	475
600	400	310	490	435	510	483
800	390	345	478	423	---	430
1000	---	---	---	---	---	---

Illinois #6 FC[illegible]

C-8

APPENDIX

Feed Material I/I #6 E starch

10.4 Sps

#	% S	FEED			AIR			i n .	SMD	Obsc	Comments	
		#/hr	psi	°F	#/hr	psi	°F					
1	H ₂ O	117	2	89	76	10	95	2	22.12	8103	H ₂ O	(X)
2	"	"	"	"	"	"	"	"	22.04	8075	REPEAT	(X)
3	"	"	3	88	110	18	94	"	12.48	8874		(1)
4	"	"	"	"	"	"	"	"	12.46	8874	REPEAT	(2)
5	"	"	4	"	143	25	95	"	9.09	9130		(3)
6	"	"	"	"	"	"	"	"	9.16	9116	REPEAT	(4)
7	"	"	5	"	182	35	"	"	5.47	9367		(5)
8	"	"	"	"	"	"	"	"	5.48	9410	REPEAT, feed rate = 11%	(6)
9	I/I #6 starch		2	88	76	10	95	"	43.31	6418		(7)
10	"		3	88	110	17	95	"		3	BAD	(X)
11	"		13	"	184	37	"	"			"	(X)
12	"	"	"	"	"	"	"	"	28.47	5365		(8)
13	"	"	10	"	143	26	"	"	52.20	4057	(52.20)	(9)
14	"	"	"	"	"	"	"	"	52.80	3859	REPEAT	(10)
15	"		8	"	112	19	"	"			BAD	(K)
16	"	"	4	"	"	18	"	"	48.36	4663	RESTARTED E screen basket	(11)
17	"	"	5	"	143	27	"	"	38.64	6495		(12)
18	"	"	"	"	"	"	"	"	36.01	4481	REPEAT	(13)
19	"	"	"	"	"	"	"	"	33.51	4495	REPEAT	(14)
20	"	"	10	"	183	37	"	"	23.98	5763		(15)
21	"	"	"	"	"	"	"	"	26.34	5591		(16)
22	"	"	"	"	"	"	"	"	26.21	5556		(17)
23	"		7	"	112	19	"	"			BAD	(18)
24	"	"	10	"	"	"	"	"	59.82	3185		(19)
25	"	"	10	"	"	"	"	"	71.11	3107		(20)
26	"	"	8	"	76	10	"	"	119.24	1838		(21)
27	"	"	"	"	"	"	"	"	119.27	1866		(22)

128 ppt feed rate of slurry @ end

MALVERN

Instruments M7.88 Tue 2 Jul 1991 Time 5:47 pm

Illinois #6 with corn starch, 2" from AGT nozzle, no cutter
 117# fuel, 10 psi, 91 F temp
 183# air, 37 psi, 95 F temp

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw070291
564	100	0.85	53.0	57.2	1.97	Record No. = 17
487	99.1	2.28	45.8	55.2	2.25	Focal length = 300 mm.
420	96.9	3.36	39.5	53.0	2.90	Presentation = lds
362	93.5	5.99	34.1	50.1	2.98	Volume distribution
313	89.5	4.30	29.5	46.1	5.42	Beam length = 54.0 mm.
270	85.2	4.18	25.4	40.7	6.08	Obscuration = 0.5556
233	81.0	3.70	21.9	34.6	6.13	Volume Conc. = 0.0119 %
201	77.3	2.83	18.9	28.4	5.74	Log. Diff. = 3.320
173	74.5	2.36	16.3	22.7	5.31	Model indp
150	72.1	2.28	14.1	17.4	4.64	D(v,0.5) = 34.02 um
129	69.9	2.26	12.1	12.8	3.48	D(v,0.9) = 317.88 um
111	67.6	2.09	10.4	9.28	2.07	D(v,0.1) = 10.85 um
96.0	65.5	2.16	9.05	7.21	1.48	D(4,3) = 101.40 um
82.5	63.4	2.06	7.80	5.73	1.42	D(2,2) = 26.21 um
71.5	61.3	2.11	6.70	4.31	1.20	Span = 9.0
61.5	59.2	2.00	5.80	3.11		Spec. surf. area 0.2289 sq. m./cc.

MALVERN

Instruments M7.88 Tue 2 Jul 1991 Time 5:52 pm

Illinois #6 with corn starch, 2" from AGT nozzle, no cutter
 1178 fuel, 8 psi, 91 F temp
 764 air, 10 psi, 95 F temp

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw070291
564	100	2.26	53.0	12.8	1.66	Record No. = 22
487	97.7	5.99	45.8	11.1	1.60	Focal length = 300 mm.
420	91.8	8.76	39.5	9.50	1.60	Presentation =1ds
362	83.0	10.3	34.1	7.90	1.61	Volume distribution
313	72.7	10.9	29.5	6.28	1.62	Beam length = 54.0 mm.
270	61.7	10.4	25.4	4.66	1.38	Obscuration =0.1866
233	51.4	8.80	21.9	3.28	1.04	Volume Conc. = 0.0136 %
201	42.6	6.15	18.9	2.24	0.70	Log. Diff. = 3.423
173	36.4	4.47	16.3	1.54	0.47	Model indep
150	31.9	3.87	14.1	1.07	0.33	D(v,0.5) = 227.73 µm
129	28.1	3.55	12.1	0.74	0.23	D(v,0.9) = 406.31 µm
111	24.5	2.89	10.4	0.51	0.15	D(v,0.1) = 41.43 µm
96.0	21.6	2.67	9.05	0.38	0.11	D(4,3) = 224.37 µm
82.5	19.0	2.23	7.80	0.25	0.09	D(3,2) = 119.27 µm
71.5	16.7	2.11	6.70	0.16	0.06	Span = 1.6
61.5	14.6	1.86	5.80	0.10		Spec. surf. area 0.0503 sq. m./cc.

Feed Material Ill. #6 Filter cake

#	% S	FEED			AIR			i n	SMD	Obsc	Comments
		#/hr	psi	°F	#/hr	psi	°F				
23	H ₂ O	118	1	86	76	10	89	2	24.36	7535	H ₂ O
24	"	"	"	"	"	"	"	"	24.26	7461	
25	"	"	4	85	183	35	88	"	7.87	8906	
26	"	"	"	"	"	"	"	"	7.94	8901	
27	F/C	"	18	"	182	36	"	"	40.82	3425	Illinois #6 Filter cake
28	"	"	24	"	"	"	"	"	45.59	3408	
29	"	"	"	"	"	"	"	"	51.01	3499	
30	"	"	"	"	"	"	"	"	42.32	3626	
31	"	"	21	"	142	26	"	"	68.52	2404	
32	"	"	36	"	"	"	"	"	70.81	2	
33	"	"	37	"	"	"	"	"	65.27	2501	
34	"	"	39	"	112	19	"	"	90.97	1818	
35	"	"	38	"	"	"	"	"	113.03	1497	
36	"	"	40	"	"	"	"	"	114.07	1866	drops on lens
37	"	"	42	"	"	"	"	"	119.63	1712	
38	"	"	41	"	80	12	"	"	201.07	0991	
39	"	"	"	"	"	"	"	"	205.02	1087	
40	"	"	38	"	182	36	"	"	77.21	2760	drops on lens
41	"	"	"	"	"	"	"	"	82.17	2735	
42	"	"	"	"	"	"	"	"	73.68	3026	
21											
22											
23											
24											
25											
26											
27											

126 PPH

1130 AWT

MALVERN

Instruments M7.88 Wed 3 Jul 1991 Time 11:41 am

H2O
118# fuel, 1 psi, 86 F temp
76# air, 10 psi, 89 F temp

2" from AGT nozzle, no cutter

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw070391
564	100	0.20	53.0	61.4	4.38	Record No. = 24
487	99.8	0.58	45.8	57.0	4.96	Focal length = 300 mm.
420	99.2	0.94	39.5	52.1	5.55	Presentation = lds
362	98.3	1.25	34.1	46.5	5.77	Volume distribution
313	97.0	1.56	29.5	40.7	5.78	Beam length = 54.0 mm.
270	95.5	1.82	25.4	35.0	5.36	Obscuration = 0.7461
233	93.7	2.07	21.9	29.6	4.76	Volume Conc. = 0.0184 %
201	91.6	2.29	18.9	24.8	4.21	Log. Diff. = 3.413
173	89.3	2.64	16.3	20.6	3.55	Model indp
150	86.7	3.02	14.1	17.1	2.72	D(v,0.5) = 37.36 μm
129	83.6	3.29	12.1	14.4	2.26	D(v,0.9) = 180.67 μm
111	80.4	3.45	10.4	12.1	1.86	D(v,0.1) = 8.88 μm
96.0	76.9	3.76	9.05	10.2	1.91	D(4,3) = 65.26 μm
82.5	73.1	3.66	7.80	8.33	2.05	D(3,2) = 24.26 μm
71.5	69.5	3.97	6.70	6.28	1.68	Span = 4.6
61.5	65.5	4.10	5.80	4.60		Spec. surf. area 0.2473 sq.m./cc.

MALVERN

Instruments M7.88 Wed 3 Jul 1991 Time 11:45 am

Illinois #6 filter cake 2" from AGT nozzle, no cutter
 118# fuel, 18 psi, 85 F temp
 182# air, 36 psi, 88 F temp

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw070391
564	100	1.59	53.0	36.1	1.81	Record No. = 27
487	98.4	4.23	45.8	34.2	2.12	Focal length = 300 mm.
420	94.2	6.19	39.5	32.1	2.71	Presentation = lds
362	88.0	7.25	34.1	29.4	2.87	Volume distribution
313	80.7	7.68	29.5	26.5	2.73	Beam length = 54.0 mm.
270	73.1	7.27	25.4	23.8	2.60	Obscuration = 0.3425
233	65.8	6.13	21.9	21.2	3.05	Volume Conc. = 0.0089 %
201	59.7	4.24	18.9	18.2	4.68	Log. Diff. = 3.491
173	55.4	3.34	16.3	13.5	4.41	Model indp
150	52.1	3.24	14.1	9.06	2.23	D(v,0.5) = 136.04 μm
129	48.9	2.94	12.1	6.83	1.03	D(v,0.9) = 378.43 μm
111	45.9	2.20	10.4	5.80	0.47	D(v,0.1) = 14.60 μm
96.0	43.7	2.05	9.05	5.33	0.54	D(4,3) = 162.86 μm
82.5	41.7	1.90	7.80	4.79	0.88	D(3,2) = 40.82 μm
71.5	39.8	1.92	6.70	3.91	0.90	Span = 2.7
61.5	37.8	1.80	5.80	3.01		Spec. surf. area 0.1470 sq.m./cc.

MALVERN

Instruments M7.88 Wed 3 Jul 1991 Time 11:58 am

Illinois #6 filter cake 2" from AGT nozzle, no cutter
 118# fuel, 41 psi, 91 F temp
 80# air, 12 psi, 90 F temp

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw070391
564	100	3.61	53.0	5.38	0.60	Record No. = 39
487	96.4	9.44	45.8	4.79	0.60	Focal length = 300 mm.
420	86.9	13.5	39.5	4.19	0.61	Presentation = lds
362	73.4	15.4	34.1	3.58	0.65	Volume distribution
313	58.1	15.5	29.5	2.93	0.72	Beam length = 54.0 mm.
270	42.6	13.5	25.4	2.21	0.64	Obscuration = 0.1087
233	29.1	9.67	21.9	1.57	0.49	Volume Conc. = 0.0132 %
201	19.4	3.98	18.9	1.08	0.32	Log. Diff. = 4.684
173	15.4	2.01	16.3	0.77	0.21	Model indp
150	13.4	2.32	14.1	0.56	0.16	D(v,0.5) = 289.59 µm
129	11.1	1.98	12.1	0.40	0.13	D(v,0.9) = 437.24 µm
111	9.11	1.08	10.4	0.27	0.09	D(v,0.1) = 119.68 µm
96.0	8.04	0.76	9.05	0.18	0.07	D(4,3) = 286.74 µm
82.5	7.28	0.63	7.80	0.11	0.05	D(3,2) = 205.02 µm
71.5	6.65	0.64	6.70	0.07	0.03	Span = 1.1
61.5	6.01	0.63	5.80	0.04		Spec. surf. area 0.0293 sq. m./cc.

10.5 fcs

[illegible]

MALVERN

Instruments M7.88 Fri 12 Jul 1991 Time 2:45 pm

Battelle Elkhorn
 1204 fuel, 5 psi, 91 F temp
 764 air, 12 psi, 93 F temp

2.0" from AGT nozzle, no cutter

Size microns	% under	% in band	Size microns	% under	% in band	Result source=jw071291
564	100	1.04	53.0	27.0	3.17	Record No. = 3
487	99.0	2.84	45.8	23.8	3.12	Focal length = 300 mm.
420	96.1	4.32	39.5	20.7	3.01	Presentation = lds
362	91.8	5.34	34.1	17.7	3.18	Volume distribution
313	86.5	6.06	29.5	14.5	3.54	Beam length = 54.0 mm.
270	80.4	6.37	25.4	11.0	3.12	Obscuration = 0.3512
233	74.0	6.32	21.9	7.85	2.33	Volume Conc. = 0.0164 %
201	67.7	5.85	18.9	5.52	1.57	Log. Diff. = 3.309
173	61.9	5.03	16.3	3.94	1.13	Model indep
150	56.8	4.49	14.1	2.81	0.94	D(v,0.5) = 119.36 µm
129	52.3	4.62	12.1	1.88	0.72	D(v,0.9) = 343.46 µm
111	47.7	4.73	10.4	1.15	0.45	D(v,0.1) = 24.35 µm
96.0	43.0	4.78	9.05	0.70	0.28	D(4,3) = 151.48 µm
82.5	38.2	4.02	7.80	0.42	0.18	D(3,2) = 67.03 µm
71.5	34.2	3.81	6.70	0.24	0.10	Span = 2.7
61.5	30.4	3.41	5.80	0.14		Spec. surf. area 0.0895 sq. m./cc.

MALVERN

Instruments M7.08 Fri 12 Jul 1991 Time 2:55 pm

Battelle, Elkhorn
 1200 fuel, 8 psi, 91 F temp
 1840 air, 41 psi, 93 F temp

2.0" from AGT nozzle, no cutter

Size microns	% under	% in band	Size microns	% under	% in band
56.4	100	0.70	53.0	50.5	2.73
487	99.3	1.91	45.8	47.8	2.81
420	97.4	2.88	39.5	44.9	3.04
362	94.5	3.53	34.1	41.9	3.65
313	91.0	3.97	29.5	38.3	4.66
270	87.0	4.10	25.4	33.6	5.20
233	82.9	3.98	21.9	28.4	5.86
201	78.9	3.99	18.4	23.1	4.77
173	75.3	3.34	16.3	18.4	4.27
150	72.0	3.34	14.1	14.1	3.65
129	68.7	2.34	12.1	10.4	2.91
111	65.3	2.11	10.4	7.54	1.96
96.0	62.2	1.13	9.05	5.58	1.50
82.5	59.1	2.83	7.80	4.08	1.27
71.5	56.2	2.92	6.70	2.81	0.91
61.5	53.3	2.84	5.80	1.90	

Result source=jw071291
 Record No. = 13
 Focal length = 300 mm.
 Presentation = lds
 Volume distribution
 Beam length = 54.0 mm.
 Obscuration = 0.5740
 Volume Conc. = 0.0148 %
 Log. Diff. = 2.821
 Model indep
 D(v,0.5) = 51.66 μm
 D(v,0.9) = 300.94 μm
 D(v,0.1) = 11.91 μm
 D(4,3) = 103.83 μm
 D(3,2) = 30.94 μm
 Span = 5.6
 Spec. surf. area
 0.1939 sq. m./cc.

APPENDIX D

COAL ANALYSES

APPENDIX D

COAL ANALYSES

Attached are Commercial Testing and Engineering chemical analyses for the cleaned Illinois No. 6, see Table D-1. A particle size distribution of the cleaned Illinois coal is presented as Table D-2. A particle size distribution is provided for the cleaned Utah coal in Tables D-3.

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • (708) 953-9300

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

August 1, 1991

PLEASE ADDRESS ALL CORRESPONDENCE TO
16130 VAN DRUNEN RD., P.O. BOX 127
SOUTH HOLLAND, IL 60473
TELEPHONE (708) 331-2900
FAX (708) 333-3060

BATTELLE MEMORIAL INSTITUTE
Columbus Laboratories
505 King Avenue
Columbus, OH 43201
ATTN: J.K. Raghavan, Ph.D.
Rm. 13-3-043

Sample identification by
Battelle Memorial Institute

Kind of sample
reported to us Filter Cake

Sample ID: Illinois #6
Flotation Filter Cake
Date: May, 1991

Sample taken at Battelle Memorial Institute

Sample taken by Battelle Memorial Institute

Date sampled -----

P.O. No. A-3658

Date received July 15, 1991

Analysis Report No. 71-16352

Page 1 of 3

PROXIMATE ANALYSIS

	<u>As Received</u>	<u>Dry Basis</u>	
% Moisture	19.58	xxxxxx	
% Ash	4.01	4.99	
% Volatile	27.87	34.66	
% Fixed Carbon	48.54	60.35	
	100.00	100.00	
Btu/lb	10853	13495	MAF 14204
% Sulfur	1.92	2.39	
Alkalies as Sodium Oxide	0.07	0.09	

FUSION TEMPERATURE OF ASH, (°F)

	<u>Reducing</u>	<u>Oxidizing</u>
Initial Deformation (IT)	1975	2480
Softening (ST)	2120	2520
Hemispherical (HT)	2260	2555
Fluid (FT)	2400	2590

Respectfully submitted
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • (708) 953-9300

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

August 1, 1991

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD., P.O. BOX 127
SOUTH HOLLAND, IL 60473
TELEPHONE: (708) 331-2900
FAX: (708) 333-3060

BATTELLE MEMORIAL INSTITUTE
Columbus Laboratories
505 King Avenue
Columbus, OH 43201
ATTN: J.K. Raghavan, Ph.D.
Rm. 13-3-043

Sample identification by
Battelle Memorial Institute

Kind of sample
reported to us Filter Cake

Sample ID: Illinois #6
Flotation Filter Cake
Date: May, 1991

Sample taken at Battelle Memorial Institute

Sample taken by Battelle Memorial Institute

Date sampled -----

P.O. No. A-3658

Date received July 15, 1991

Analysis Report No. 71-16352

Page 2 of 3

ANALYSIS OF ASH

WEIGHT %, IGNITED BASIS

Silicon dioxide	46.44
Aluminum oxide	20.55
Titanium dioxide	1.92

Iron oxide	24.18
Calcium oxide	2.18
Magnesium oxide	1.00
Potassium oxide	2.50
Sodium oxide	0.21

Sulfur trioxide	0.66
Phosphorus pentoxide	0.15
Strontium oxide	0.03
Barium oxide	0.02
Manganese oxide	0.16
Undetermined	0.00
	100.00

Silica Value = 62.93
Base:Acid Ratio = 0.44
True Temperature = 2369 °F

Type of Ash = BITUMINOUS
Fouling Index = 0.09
Slagging Index = 1.05

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO

John Hall
Manager, South Holland Laboratory

TABLE D-1. CHEMICAL ANALYSIS OF CLEANED ILLINOIS NO. 6, DELTA MINE COAL
(CLEANED BY CONVENTIONAL FROTH FLOTATION AT AMAX)

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • (708) 953-9300

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

August 1, 1991

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD., P.O. BOX 127
SOUTH HOLLAND, IL 60473
TELEPHONE: (708) 331-2900
FAX: (708) 333-3060

BATTELLE MEMORIAL INSTITUTE
Columbus Laboratories
505 King Avenue
Columbus, OH 43201
ATTN: J.K. Raghavan, Ph.D.
Rm. 13-3-043

Sample identification by
Battelle Memorial Institute

Kind of sample
reported to us Filter Cake

Sample ID: Illinois #6
Flotation Filter Cake
Date: May, 1991

Sample taken at Battelle Memorial Institute

Sample taken by Battelle Memorial Institute

Date sampled -----

P.O. No. A-3658

Date received July 15, 1991

Analysis Report No. 71-16352

Page 3 of 3

OXIDATION INDEX

Z T 89.5

Respectfully submitted
COMMERCIAL TESTING & ENGINEERING CO.

Steven Hall
Manager, South Holland Laboratory

TABLE D-2. PARTICLE SIZE DISTRIBUTIONS OF MICRONIZED
ILLINOIS DELTA MINE FLOTATION FEED AND CLEAN COAL^(a)

Particle Size, μm	Weight Passing, %	
	Feed	Clean Coal
75	99.74	99.87
53	99.09	99.58
45	98.81	98.89
38	97.84	98.56
30	94.49	96.14
20	78.92	80.03
15	67.32	69.89
10	47.25	46.27
8	35.28	32.75
6	21.40	17.93
4	8.71	7.45
3	5.05	4.16
2	2.37	2.24
1	0.67	0.81
Mass Mean Diameter, μm ^(b)	13.7	13.3

- ^a Combination of sieving and SediGraph determinations.
^b Calculated from particle size distribution.

TABLE D-3. PARTICLE SIZE DISTRIBUTIONS OF MICRONIZED
UTAH SKYLINE MINE FLOTATION FEED AND CLEAN COAL^(a)

Particle Size, μm	Weight Passing, %	
	Feed	Clean Coal
75	99.56	99.86
53	99.07	99.63
45	98.03	98.82
38	97.24	98.45
30	93.22	95.61
20	73.07	84.40
15	58.81	73.87
10	40.87	53.86
8	32.05	41.59
6	23.52	30.78
4	15.83	18.62
3	10.76	11.83
2	5.75	5.73
1	1.63	1.39
Mass Mean Diameter, $\mu\text{m}^{(b)}$	14.9	11.8

^a Combination of sieving and SediGraph determinations.

^b Calculated from particle size distribution.

END

**DATE
FILMED
9 / 17 / 92**