5
RECEIVED BY TIC JAN 22 1976

OR-2015
ERDA/SPL/954144-75/1

SILICON RIBBON GROWTH BY A CAPILLARY
ACTION SHAPING TECHNIQUE

G. H. Schwuttke, Principal Investigator, 914-897-3140
International Business Machines Corporation
System Products Division, East Fishkill Laboratories
Hopewell Junction, New York 12533

Quarterly Technical Progress Report Number 1
August 1975

prepared by

G. H. Schwuttke, T. F. Ciszek, and A. Kran

Under JPL Contract Number: 954144
(Subcontract under NASA Contract NAS7-100)
(Task Order No. RD-152)
Effective Date of Contract: 5/8/75
Contract Expiration Date: 12/31/76

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
fy

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

CONTENTS

	<u>Page</u>
Technical Content Statement.....	ii
Research Program Plan.....	iii/iv
Second Quarter Activity Plan.....	v
Abstract.....	vii
Chapter 1 CRYSTAL GROWTH.....	1
Appendix I MELT GROWTH OF CRYSTALLINE SILICON TUBES BY A CAPILLARY ACTION SHAPING TECHNIQUE..	14
Appendix II MAXIMUM GROWTH RATES FOR MELT-GROWN RIBBON-SHAPED CRYSTALS.....	32
Chapter 2 RIBBON CHARACTERIZATION.....	43
Chapter 3 ECONOMIC EVALUATION AND COMPUTER-AIDED SIMULATION.....	70
Appendix I MATHEMATICAL MODEL.....	78
Appendix II LISTING OF APL FUNCTIONS.....	86

TECHNICAL CONTENT STATEMENT

This report contains information prepared by the International Business Machines Corporation under JPL subcontract. Its contents are not necessarily endorsed by the Jet Propulsion Laboratory, California Institute of Technology, or by the National Aeronautics and Space Administration.

RESEARCH PROGRAM PLAN

OBJECTIVES

1. Technological assessment of ribbon growth of silicon by a capillary action shaping technique.
2. Economic evaluation of ribbon silicon grown by a capillary action shaping technique as low-cost silicon.

SYNOPSIS OF PROGRAM OF STUDY

1. Crystal growth of silicon ribbons.
2. Characterization of silicon ribbons.
3. Economic evaluations and computer-aided simulation of ribbon growth.

SECOND QUARTER ACTIVITY PLAN

CRYSTAL GROWTH

- o Die evaluation studies utilizing machined dies of materials listed in this report.
- o Implementation of halogen bake-out procedures for graphite dies.
- o Process improvement for 25-mm-wide Si ribbon growth from graphite dies.
- o Continuation of ribbon doping studies.

CRYSTAL CHARACTERIZATION

- o Orientation measurements will be made using the ECP technique on 1-cm and 2.5-cm ribbons.
- o Perfection and orientation measurements on 1-cm and 2.5-cm ribbons will be made using transmission electron microscopy.
- o Seed-ribbon interface studies will be made for different seed orientations.

- o Solar cells will be made from 2.5-cm-wide ribbons and compared to Solar Cells made from Czochralski 2-1/4-inch-diameter silicon wafers.

ECONOMIC EVALUATION AND COMPUTER-AIDED SIMULATION

- o Using similar methodology, a module representing Czochralski crystal-pulling will be developed.
- o A series of simulation experiments will be performed with the ribbon-pulling model. Inputs from JPL could be incorporated into our studies.

ABSTRACT

Progress during the first quarter of the contractual effort is described. The work performed relates (a) to ribbon growth by a capillary action shaping technique, (b) to ribbon characterization, and (c) to economic evaluation and computer-aided simulation of ribbon growth. Actual progress includes growth of 12-mm and 25-mm-wide ribbon with individual lengths ranging from 0.12 to 1.06 meters. The growth of silicon tubes of 6-mm diameter, 1-mm wall thickness, and more than 100-cm length was also accomplished. The "growth rate" problem of melt-grown ribbon-shaped crystals was addressed. An expression for maximum growth rate of cylindrical (Czochralski geometry) crystals and ribbon-shaped crystals was derived. Some representative values at 7.5-cm diameter or width are 45 cm/hr or 2000 cm³/hr for a cylindrical Czochralski-grown crystal and 625 cm/hr or 95 cm³/hr for a 0.02-cm-thick ribbon.

The characterization effort concentrated on some "obvious" problems encountered during ribbon growth using a capillary die made from graphite. Such problems include precipitation

of particles in the orifice of the die which subsequently disturbed ribbon growth. Such particles were identified as beta silicon carbide. Thin film deposits on as-grown ribbons were identified as SiO deposits. Finally, a new approach for crystal orientation analysis of ribbons is described. This technique uses computer-generated electron channeling patterns (ECP's). A set of representative maps generated for 30-keV electron ((001), (011), and (111) poles) is included in this report.

The economic evaluation and computer-aided simulation effort describes a model conceived to simulate ribbon-pulling. Specific objectives of this computer-aided modeling effort are described. A special effort is made to describe the model in conventional mathematical terms. The model structure consists of 14 equations and 23 assigned process and economic parameters relating to the fabrication of silicon ribbon from poly-crystalline material.

Chapter 1

CRYSTAL GROWTH

T. F. Ciszek

INTRODUCTION

The crystal growth method under investigation is a capillary action shaping technique. Meniscus shaping for the desired ribbon geometry occurs at the vertex of a wettable die. As ribbon growth depletes the melt meniscus, capillary action supplies replacement material. The configuration of the technique which has been used in our initial studies is shown in Fig. 1 and is similar to the EFG process described by LaBelle (1). The crystal growth method has been applied to silicon ribbons for several years (2,3,4), and long ribbons up to 25 mm in width have been produced.

Certain problems still await solution before the technique becomes viable for large-scale economical photovoltaic applications. High-density graphite fulfills the durability and wettability requirements of a die (2) and has been used to date for most silicon ribbon growth; it is not, however, completely non-reactive. Good crystallographic perfection has been achieved on small ribbon segments (2,3), but the

Fig. 1. A schematic diagram of the capillary action shaping technique for silicon ribbon growth.

structure of large ribbons is marred by planar, line, and point defects. Our objective in this work is to attain a clearer technological assessment of silicon ribbon growth by the capillary action shaping technique and to enhance the applicability of the technique to photovoltaic power device material.

The first-quarter progress in crystal growth will be presented in four sections: 1. Description of experimental apparatus, 2. Silicon ribbon growth, 3. Silicon tube growth, and 4. Maximum growth rates for melt grown ribbon-shaped crystals.

1. Description of Experimental Apparatus

Silicon ribbon growth was conducted using a hydraulically actuated pulling mechanism with a 1.37-m maximum stroke. A pressurized air-over-oil reservoir system provided the driving force for actuation of the moving platen upon which the seed holding shaft was attached. X-Y-Z adjustment was provided for the seed shaft. Platen speed adjustment was attained via a needle valve in the oil flow line between the hydraulic cylinder and the oil reservoir tank. The crystal growth furnace and associated vacuum system were supported on the frame of the hydraulic puller (Fig. 2). The furnace was powered by a 50-kW, 450-kc-rf generator.

Fig. 2. Ribbon growth apparatus.

The furnace consisted of a single-walled 94-mm-diameter quartz shell with water-cooled stainless-steel end fittings sealed by viton O-rings. The top fitting could be either completely sealed (for vacuum bake-out of dies and furnace components) or provided with an oval cross section pull port through which the growing ribbon passed. The bottom fitting connected the shell to a horizontal base on one arm of a "tee" fitting. A horizontal sliding plate on an X-Y- θ stage was mounted on the opposite arm of the "tee". This plate held the pedestal shaft upon which the crucible assembly rested. The plate also supported an optical temperature sensor which was focused on the bottom of the crucible holder and was part of the closed-loop temperature control system. The third arm of the "tee" was used for evacuation and as a purge gas inlet.

The furnace hot zone is depicted in Fig. 3. All interior components are graphite except the opaque quartz heat shield and the clear quartz crucible. A 50-mm-O.D. x 25-mm-high flat-bottomed crucible was used. The die design depicted in Fig. 4 has been used for our initial experiments. The dies were fabricated from Poco DFP-3-2 graphite. For the initial growth attempts, the dies were typically 12.5 mm wide. The capillary slot dimension was 0.26 mm, and the die top thickness was .5 mm.

Fig. 3. Furnace hot-zone components.

Fig. 4. Capillary die.

2. Silicon Ribbon Growth

Ten ribbons of approximately 12 mm width were grown from six silicon melts in twelve growth attempts. The total length at full width of these ribbons was 4.9 meters, with individual lengths ranging from 0.12 to 1.06 meters. These ribbons were grown using our existing technology to establish a base line process, which will be analyzed and improved during the course of the contract. A second objective in growing these ribbons was training of a new ribbon growth technician who will perform the majority of ribbon growth experiments during the course of the contract.

The ribbons were grown from graphite dies which were baked out at approximately 1500°C in vacuum prior to use.

First attempts at boron doping were made on a few of the ribbons. A boron/silicon alloy powder of 1.1 parts per thousand was used as the source. 2.5×10^{-4} grams of source per gram of silicon was put into the crucible with the silicon charge. The resistivity of the resultant ribbons ranged from 0.9 to about 8 ohm-cm, as measured on the as-grown surface. More detailed analysis of the resistivity variations is in progress.

After the 50-gram silicon charge had melted, growth was initiated by touching a 3-mm-wide x 0.4-mm-thick silicon seed to the melt at the die top. A short portion of the seed was melted back, and then the pulling speed was gradually increased and the temperature adjusted to first neck the growth to a width less than that of the seed and then widen the growing ribbon to full width. The growth rate of the ribbons was 2.1 to 2.5 cm/min.

The following materials have been collected for evaluation as capillary dies in molten silicon:

- Zirconium Boride (hot pressed)
- Titanium Boride (hot pressed)
- Boron Carbide (hot pressed)
- Aluminum Boride
- Silicon Nitride
- Silicon Carbide (recrystallized)
- Vitreous Carbon

In addition, aluminum carbide was procured in hot-pressed form, but crumbled to a powder during storage. Dies of the type shown in Fig. 4 (but with thicker slots and tops) have been diamond-machined from these materials and will be

evaluated during the next quarter. Some preliminary experiments have been made with re-crystallized silicon carbide dies. While wetting and durability were adequate, evidence of contamination was seen in some ribbon segments - possibly a consequence of impurities in the silicon carbide.

Twenty-nine growth attempts were made in efforts to extend ribbon width to 25 mm. The majority of the attempts were plagued with an apparent asymmetry in temperature across the die top. However, seven full-width, doped ribbons were produced, the longest of which was 0.9 m in length (Fig. 5). Work will continue on wide ribbons during the next quarter.

3. Silicon Tube Growth

Prior to the contract starting date, dies and components for the growth of silicon tubes were designed. The growth of silicon tubes allows independent variation of growth rate and system temperature. Thus the dependence of tube wall thickness upon each parameter can be studied. In contrast, growth rate and temperature cannot easily be independently varied during ribbon growth without causing narrowing of the ribbon. The tube can be considered to be an "edgeless" ribbon and thus no "edges" are present to recede from the

Fig. 5. A 25-mm-wide and 12-mm-wide silicon ribbon.

ends of the die as is the case for ribbons when either temperature or pulling speed are increased independently. Four tubes over one meter in length, nominally 1 mm in wall thickness and about 6 mm in diameter were grown during this quarter. The dependence of tube geometry upon growth parameters and also some physical characteristics of the tubes are detailed in the attached paper (Appendix I).

4. Maximum Growth Rates for Melt Grown Ribbon-Shaped Crystals

From heat balance considerations at the growing interface and an assumption of predominantly radiative heat loss from the surface, an expression for the maximum growth rate of melt-grown, ribbon-shaped crystals has been derived. For a given material and a large width-to-thickness ratio W/t , the maximum growth rate varies as $t^{-1/2}$ and is independent of W . A comparison of maximum cylindrical and ribbon growth rates was made for the silicon system. Some representative values at 7.5-cm diameter or width are 45 cm/hr or 2000^3 cm³/hr for a cylindrical Czochralski-grown crystal and 625 cm/hr or 95 cm³/hr for a 0.02-cm-thick ribbon. For details see Appendix II.

REFERENCES

1. H. E. LaBelle, Jr., Mater. Res. Bull. 6, 581 (1971).
2. T. F. Ciszek, Mater. Res. Bull. 7, 731 (1972).
3. T. F. Ciszek and G. H. Schwuttke, Phys. Stat. Sol. (a) 27, 231 (1975).
4. J. C. Swartz, T. Surek, and B. Chalmers, J. Electron. Mater. 4, 255 (1975).

ACKNOWLEDGMENT

Technical support in crystal growing was provided for by F. Newman.

MELT GROWTH OF CRYSTALLINE
SILICON TUBES BY A CAPILLARY
ACTION SHAPING TECHNIQUE
BY

T. F. CISZEK

INTERNATIONAL BUSINESS MACHINES CORPORATION
EAST FISHKILL LABORATORIES, HOPEWELL JUNCTION, N.Y.

ABSTRACT

Silicon tubes 6 mm in diameter and over 1 m long were grown by a capillary action shaping technique using a 7 mm diameter graphite capillary die with a 1.3 mm thick wall. Diameter and wall thickness could be varied from 6.6 to 5.7 mm and 1.2 to 0.4 mm respectively by relative system temperature changes of up to 6.7°C or growth rate variations in the range 11 to 21 mm/min. The tubes were doped with boron to a 2 ohm-cm resistivity. Planar defects and some large angle grain boundaries were present, with the largest grains extending over one quarter of the tube circumference.

1. INTRODUCTION

The melt growth of crystalline silicon is usually effected by the well-known Czochralski and float-zoning techniques, which produce solid cylindrical single crystals. Ribbon shaped silicon has also been solidified by several techniques. The dendritic web

growth method ^(1,2) entails the solidification of a silicon sheet from a melt meniscus which is bounded at the ends by thin dendrites growing downward into a super-cooled melt region and bounded at the top by the ribbon/melt interface. The Stepanov method ^(3,4) utilizes a non-wetting die, in contact with the melt, to shape the meniscus for ribbon growth. The edge-defined, film-fed technique ⁽⁵⁾ has more recently been applied to silicon ribbon growth. ^(6,7,8) In this method, a wetted die contacts the melt and capillary action causes the melt to rise to the top die surface where meniscus shaping takes place. The lower boundary of the meniscus is attached to the die top and conforms to its shape.

In this paper, the previously mentioned capillary action shaping technique has been applied to the melt growth of silicon tubes. A photograph of a silicon tube and ribbon grown by this technique appears in Fig. 1.

Polycrystalline tubes of silicon have previously been produced by a chemical vapor deposition process ⁽⁹⁾ on graphite cylinder substrates in sizes up to 100 mm diameter by 1.8 m long. The grain size of such tubes is extremely small, compared to that of melt grown tubes.

Fig. 1. A 12-mm-wide silicon ribbon and a 6-mm-diameter silicon tube grown by the capillary action shaping technique.

2. TUBE GROWTH

The capillary action shaping technique for silicon tube growth is shown schematically in Fig. 2. A 5 cm diameter quartz crucible resting in a conductive, rf heated susceptor held a 50 gram silicon charge. A high density graphite capillary die composed of two concentric cylinders was immersed in the liquid silicon, and supported by a holding plate (not shown in Fig. 2) slightly below its top surface. The die top was 7 mm O.D. by 4.4 mm I.D. with a 0.64 mm thick capillary slot. Two horizontal heat shields were concentrically placed above the die and holder; the upper shield is visible in Fig. 3.

Thin $\langle 111 \rangle$ axis seeds were used to initiate growth at some point of the capillary slot (Fig. 3a). The system temperature (as monitored by an optical radiation pyrometer with 0-10 mv voltage output) was then lowered while simultaneously increasing the upward pulling speed of the seed lifting mechanism. The growth was thus caused to spread circumferentially around the die top (Fig. 3b). Further reduction of the system temperature allowed increased spreading of the growth (Fig. 3c) until the tube walls closed. Equilibrium tube growth is pictured in Fig. 3d. Tubes were normally closed in a

Fig. 2. A schematic diagram of capillary action tube growth.

Fig. 3. Stages in the growth of a silicon tube. (a) Seeding, (b) Circumferential spreading by temperature reduction and pulling rate increase, (c) Further spreading by temperature reduction, (d) Closed, equilibrium growth.

distance of 5 - 15 cm beyond the seed, and were grown in closed lengths of over 1 meter. Growth rates were varied from 11 to 21 mm/min and had an influence on tube diameter and wall thickness, as did the system temperature.

Both growth rate and system temperature were investigated as parameters for tube diameter and wall thickness control. The temperature dependence was determined by growing a tube and gradually increasing the temperature as growth progressed beyond the point of closure. Over a growth distance of 1.03 m, the temperature was increased 6.7°C while keeping growth speed constant at 11 ± 1 mm/min. The tube was then sectioned at six positions corresponding to six different values of the system temperature; the cross sectional profiles are shown in Fig. 4. Analysis of the profiles led to the temperature dependence of average outside diameter, inside diameter, and wall thickness depicted in Fig. 5. The dependence is approximately linear in each case, with the respective magnitudes of -0.13 mm/ $^{\circ}\text{C}$, 0.08 mm/ $^{\circ}\text{C}$, and -0.105 mm/ $^{\circ}\text{C}$. The tube opened at a thin part of the wall, when the average wall thickness dropped below 0.3 mm. From Fig. 5, it can be seen that the outside diameter decreased at a faster rate than the inside diameter increased (i.e. the growing interface favored the inner wall of the die). The cause of the cross sectional irregularities evident in Fig. 4 is not unambiguously known. Possible causes

0.0M T_0

0.02M $T_0 + 0.5^\circ\text{C}$

0.26M $T_0 + 3.6^\circ\text{C}$

0.48M $T_0 + 4.7^\circ\text{C}$

0.77M $T_0 + 5.4^\circ\text{C}$

1.03M $T_0 + 6.7^\circ\text{C}$

Fig. 4. Cross-sectional profiles of a tube at various distances from point of closure and corresponding relative system temperatures.

Fig. 5. Dependence of average outside diameter, inside diameter, and wall thickness upon relative system temperature.

include temperature nonuniformity, die irregularities, surface energy/orientation effects, and degree of non-levelness of the die top.

To investigate the dependence of tube geometry upon growth rate, a tube was grown at a constant system temperature while gradually increasing the growth rate from 13.5 mm/min at the point of closure to 21 mm/min. at a distance of 1.1 meter from the point of closure. This tube was also sectioned and the profiles were measured to yield the data in Fig. 6 (the portion grown at speeds above 19 mm/min was shattered during sectioning). A non-linear monotonic decrease of outside diameter and wall thickness with increasing growth speed is seen. Again, the outside diameter decreases more rapidly than the inside diameter increases. Thus both growth rate and system temperature exert a considerable influence on tube dimensions, with a given die geometry (these two tubes were grown with the same die).

The tubes were grown in an argon atmosphere at a purge rate of 20 liters/min, exhausted through the pulling port of the furnace.

3. TUBE CHARACTERISTICS

Tube sections adjacent to those shown in Fig. 4 were chemically etched with an $\text{HF}/\text{HNO}_3/\text{CH}_3\text{COOH}/\text{H}_2\text{O}$ solution

Fig. 6. Dependence of average outside diameter, inside diameter, and wall thickness upon growth rate.

to determine the gross crystal structure. The results (see Fig. 7) indicate that the dominant defects are planar twins, twin lamella, and large area stacking faults. Large-angle grain boundaries are also present to a lesser extent. At the point of closure, a large-angle boundary is seen passing from the inner wall to the outer wall of the tube, as would be expected. The etched tube sections at closure and 2 cm after closure are shown in more detail in Fig. 8. For this particular tube, a wandering concentric grain boundary was seen approximately midway between the inner and outer walls in the section taken shortly after closure. This phenomenon was not seen in several other tubes which were examined; however, the dominance of planar defects was seen in other tubes. Note that the central region of the tube (sections at 0.26 m, 0.40 m and 0.77 m) exhibits some fairly large grains extending over approximately one quarter of the tube circumference.

Several tubes were doped p-type during growth by the addition of a boron/silicon alloy powder (concentration - 1.1 parts per thousand) to the crucible before melt down. Approximately 2.5×10^{-4} grams of this powder was used per gram of silicon charge. The resistivity of the resultant tubes was measured using a 4 - probe array with a 0.64 mm probe spacing and a 200 gram loading force. The measurements were made on the as-grown surface. The geometry

Fig. 7. Etched cross sections adjacent to those of Fig. 4.

Fig. 8. Detailed view of etched cross sections at point of closure and 2 cm below point of closure.

correction factor for an infinite sheet of thickness equal to the tube wall thickness was applied. The results are shown in Fig. 9. The values were predominantly in the range 1 - 3 ohm-cm, with a few excurrent points. The target value was 2 ohm-cm.

4. CONCLUSIONS AND DISCUSSION

Silicon tubes can be grown by a capillary action shaping technique in the sizes described herein, with the same equipment employed for ribbon growth (except of course for the die and shields). The crystal structure of the resultant tubes contains numerous planar defects and some large-angle grain boundaries and, in this respect, is similar to the structure of silicon ribbons grown by the same method.⁽⁷⁾ The observed gross defect spacing and grain size is large compared to that of CVD grown polycrystalline tubes ($< .005$ mm), with some grains extending over more than one quarter of the tube circumference.

Tubes appear to be somewhat easier to grow than ribbons, in that growth is stable over a wider range of system temperatures and growth rates. However, changes in growth rate and temperature affect the tube dimensions and, in fact, can be used to obtain various dimensions from a given die.

Fig. 9. Resistivity variations along length of two p-type, doped tubes.

While one die design was used for the work reported here, it should be possible to make tubes of smaller and larger sizes by suitable die design changes. Circumferential thermal uniformity of course must be maintained for larger tubes.

5. ACKNOWLEDGEMENTS

The technical assistance of F. Newman was very helpful in this work and thanks are extended. A portion of the work was supported by Jet Propulsion Laboratory subcontract 954144 under National Aeronautics and Space Administration contract NAS7-100 (U.S.A.).

REFERENCES

1. S. N. Dermatis and J. W. Faust, Jr., IEEE Trans. Commun. and Electronics 82, 94 (1963)
2. D. L. Barrett, E. H. Myers, D. R. Hamilton, and A. I. Bennett, J. Electrochem. Soc. 118, 952 (1971)
3. A. V. Stepanov, Zh. tekhn. Fiz. 29, 381 (1959)
4. J. Boatman and P. Goundry, Electrochem. Tech. 5, 98 (1967)
5. H. E. LaBelle, Jr., Mater. Res. Bull. 6, 581 (1971)
6. T. F. Ciszek, Mater. Res. Bull. 7, 731 (1972)
7. T. F. Ciszek and G. H. Schwuttke, Phys. Stat. Sol. (a) 27, 231 (1975)
8. J. C. Swartz, T. Surek, and B. Chalmers, J. Electron. Mater. 4, 255 (1975)
9. W. Dietze, L. P. Hunt, and D. H. Sawyer, J. Electrochem. Soc. 121, 1112 (1974)

MAXIMUM GROWTH RATES FOR MELT-GROWN RIBBON-SHAPED CRYSTALS

T. F. Ciszek

IBM East Fishkill Laboratories

Hopewell Junction, N. Y. 12533

INTRODUCTION

An analysis of heat balance at the growing interface for non-dendritic crystal growth from the melt has been made by Billig.¹ His calculation indicated that the maximum growth rate or pulling speed $v_{\max}$ would occur when the temperature gradient in the melt at the interface approached 0, and would be given by

$$v_{\max} = \frac{-K_m}{L\rho_m} \left(\frac{dT}{dx} \right)_m \quad (1)$$

where K_m = thermal conductivity of the solid crystal at the melting temperature

L = latent heat of fusion

ρ_m = density of the crystal at the melting temperature

T = crystal temperature

x = distance along crystal from the growing interface

and $\left(\frac{dT}{dx} \right)_m$ = temperature gradient in the crystal at the growing interface.

An expression for maximum growth rate of cylindrical (Czochralski geometry) crystals was obtained under the following assumptions:

1. Heat loss from the crystal is only by radiation to a cold environment.
2. The solid/liquid interface is planar.
3. The thermal conductivity of the crystal varies inversely with temperature.
4. The surface emissivity ϵ of the crystal is temperature independent.

Billig's resultant expression for $v_{\max}$ was

$$v_{\max} = \frac{1}{L\rho_m} \sqrt{\frac{2\sigma\epsilon K_m T_m^5}{3r}}, \quad (2)$$

where σ = the Stefan-Boltzmann constant

T_m = melting temperature of the crystal.

and r = crystal radius (assumed constant).

Billig's treatment contains a minor error, in that the temperature dependence of the thermal conductivity should have been introduced earlier in the derivation, thus changing the form of the differential equation governing the heat flow. A factor of $(3/2)^{1/2}$ multiplies equation (2) when the error is corrected. This corrected treatment of the cylindrical case will be extended to the geometry of a thin rectangular plate (ribbon).

THE RIBBON GEOMETRY

Under the same assumptions listed above, it is possible to calculate a maximum growth rate for non-dendritic ribbon-shaped crystals. Such crystals can be grown from the melt by several capillary action shaping techniques.²⁻⁵

These various techniques are in general conducted in such a manner that the solidification isotherm is approximately planar, and the ribbons are thin (of the order of a few millimeters or less). Thus, the analysis may be carried out as a one dimensional, linear heat flow problem.⁶ Fox⁷ has demonstrated that even if minor radial thermal gradients are present, the average temperature over planes perpendicular to the main direction of heat flow satisfies a linear heat flow equation. A one dimensional approach will be used in the following derivation.

Heat from the solidification front is dissipated by conduction along the ribbon and radiation from the ribbon surface. Heat conduction along the ribbon is given by

$$Q = AK \left(\frac{dT}{dx} \right) = WtK \left(\frac{dT}{dx} \right) \quad (3)$$

where A = ribbon cross sectional area

K = thermal conductivity of the ribbon

W = ribbon width

and t = ribbon thickness.

Heat loss from an element dS of the ribbon surface dx long via radiation to a cold environment is

$$dQ = \sigma \epsilon T^4 dS = 2(W + t)\sigma \epsilon T^4 dx. \quad (4)$$

For many materials of interest, particularly semiconductors such as silicon, the solid thermal conductivity K can be approximately expressed as $K = K_m T_m / T$ (assumption 3 above). Making this substitution in Eq. (3), and combining equations (3) and (4) we get the differential equation

$$\frac{d}{dx} [T^{-1} \left(\frac{dT}{dx} \right)] = \frac{2(W + t)\sigma \epsilon T^4}{WtK_m T_m} \quad (5)$$

The solution of (5) for boundary conditions

$$T = 0, \quad \frac{dT}{dx} = 0 \text{ at } x = \infty$$

and

$$T = T_m \text{ at } x = 0$$

is

$$T = \left[2 \left(\frac{(W + t)\sigma \epsilon}{WtK_m T_m} \right)^{1/2} x + T_m^{-2} \right]^{-1/2} \quad (6)$$

The derivative of (6) evaluated at $x = 0$ is

$$\left(\frac{dT}{dx} \right)_{x=0} = \left(\frac{dT}{dx} \right)_m = - \sqrt{\frac{\sigma \epsilon (W + t) T_m^5}{WtK_m}} \quad (7)$$

Combining Eqs. (1) and (7) results in the maximum growth rate under the stated assumptions:

$$v_{\max} = \frac{1}{L\rho_m} \sqrt{\frac{\sigma \epsilon (W + t) K_m T_m^5}{Wt}} \quad (8)$$

DISCUSSION

It is interesting to compare maximum ribbon growth rates (Eq. (8)) and maximum Czochralski growth rates for a specific material. In Fig. 1, such a comparison is made for the case of silicon. As previously mentioned, the corrected equation for maximum Czochralski growth rates should read

$$v_{\max} = \frac{1}{L\rho_m} \sqrt{\frac{\sigma\epsilon K_m T_m^5}{r}}. \quad (9)$$

Note that in terms of the perimeter to area ratio p/A , both the cylindrical and ribbon cases may be described by the same equation:

$$v_{\max} = \frac{1}{L\rho_m} \sqrt{\frac{p\sigma\epsilon K_m T_m^5}{2A}}. \quad (10)$$

The numerical values used in constructing Fig. 1 are as follows:

$$\begin{aligned} L &= 12.1 \text{ Kcal/mole}^8 \\ \rho_m &= 2.29 \text{ g/cm}^3 \\ \sigma &= 5.67 \times 10^{-8} \text{ joule/}^\circ\text{K}^4\text{-m}^2\text{-sec} \\ \epsilon &= 0.46 \\ K_m &= 0.287 \text{ watt/cm-}^\circ\text{K} \\ T_m &= 1685 \text{ }^\circ\text{K.} \end{aligned}$$

ρ_m was determined from the room temperature density⁹ of 2.33 g/cm³ and a linear thermal expansion coefficient^{10,11} of $4.5 \times 10^{-6}/^\circ\text{C}$.

Fig. 1. Maximum growth rate vs ribbon width or crystal diameter for silicon.

The emissivity¹² is a spectral value at 0.65 microns and 1685°K; ideally, total hemispherical emissivity should be used. The thermal conductivity value K_m is an extrapolation of measurements by Shanks, et al.¹³ State of the art growth rates are approximately $0.25 v_{\max}$ for silicon Czochralski growth and $0.3 v_{\max}$ for silicon ribbon growth.⁵

If the width to thickness ratio of the growing ribbon is large ($W/t \gg 1$), Eq. (8) may be simplified to

$$v_{\max} = \frac{1}{L\rho_m} \sqrt{\frac{\sigma \epsilon K_m T_m^5}{t}} \quad (11)$$

Even for $W/t = 10$, the maximum growth rate is within 5% of the rate for any greater W/t ratios as can be seen in Fig. 1. Thus, maximum growth rate is essentially independent of width for wide ribbons and varies as $t^{-1/2}$.

The curve for maximum growth rate vs. ribbon thickness from Eq. (11) is shown in Fig. 2 for the case of silicon.

Although the maximum ribbon growth rates are considerably higher than maximum Czochralski growth rates, the amount of material produced per unit time is, of course, much smaller in the case of ribbons. One way of viewing this is to consider the rate of surface area produced during crystal growth. Again for the case of silicon, 0.05 cm thick ribbons will be compared with Czochralski crystals, assuming that after

Fig. 2. Maximum growth rate vs thickness for silicon ribbon.

growth the Czochralski crystals will be sliced into 0.05 cm thick cylindrical wafers with a 50% cutting loss. We will consider only the crystal growth time (not the sawing time) for the cylindrical crystals. The rate of surface area production (at maximum growth rate) as a function of Czochralski crystal diameter or ribbon width is shown in Fig. 3. Included in the figure is the effect of simultaneous multiple ribbon growth. For example, four 2.5 cm wide ribbons or one 10 cm wide ribbon generates surface area at the same rate as a 2.5 cm diameter Czochralski crystal; eight 10 cm wide ribbons or one 80 cm wide ribbon generates area at the same rate as a 10 cm diameter Czochralski crystal. Current state of the art stands at about 3 cm for silicon ribbon width and 10 cm for silicon Czochralski crystal diameter.

The assumptions underlying the maximum growth rate derivation are reasonable for conventional growth systems, but, of course, in the final analysis $(dT/dx)_m$ is an independent system variable which can be varied over a wide range by manipulation of heat sources and sinks. In such systems, or in dendritic growth systems, it is possible that the observed maximum growth rates may deviate considerably from those predicted by Eq. (8).

Fig. 3. Rate of surface area production during growth vs Czochralski crystal diameter or ribbon width. A 0.05-cm ribbon thickness and post-growth slicing of the Czochralski crystal into 0.05-cm-thick wafers with 50% material loss are assumed. Maximum silicon growth rates are used.

REFERENCES

1. E. Billig, Proc. Roy. Soc. 229, 346 (1955).
2. A. V. Stepanov, Bull. Acad. Sci. (U.S.S.R.) 33, 1775 (1969).
3. J. Boatman and P. Goundry, Electrochem. Tech. 5, 98 (1967).
4. H. E. LaBelle, Jr., Mat. Res. Bull. 6, 581 (1971).
5. T. F. Ciszek and G. H. Schwuttke, Phys. Stat. Sol. (a) 27, 231 (1975).
6. See for example the treatment of rectangular cooling fins by H. S. Carslaw and J. C. Jaeger, Conduction of Heat in Solids (Oxford University Press, 1959) p. 141.
7. Fox, Phil. Mag. 18, 209 (1934).
8. R. E. Honig, RCA Review 23, 567 (1962).
9. H. J. McSkimin, W. L. Bond, E. Buehler, and G. K. Teal, Phys. Rev. 83, 1080L (1951).
10. D. F. Gibbons, Phys. Rev. 112, 136 (1958).
11. L. Maissel, J. Appl. Phys. 31, 211L (1960).
12. F. G. Allen, J. Appl. Phys. 101, 1676 (1956).
13. H. R. Shanks, P. D. Maycock, P. H. Sidles, and G. C. Danielson, Phys. Rev. 130, 1743 (1963).

Chapter 2

RIBBON CHARACTERIZATION

G. H. Schwuttke, H. Kappert, and R. C. Wnuk

INTRODUCTION

The characterization effort during the first quarterly reporting period addresses some "obvious" problems related to the growth of ribbons using carbon dies. These problems pertain to the "coating" of carbon that occurs if a carbon die is placed into molten silicon. As a consequence the growth of crystallites is observed in the orifice of the die. Such crystallites have been reported before to disturb the growth process (Ref. 1,2). Complete positive identification of such crystals has not yet been presented. Another object of general interest is the presence of brownish-looking films on as-grown silicon ribbons. An analysis of such films was also made during the reporting period. The last point addressed during the first quarter was the computer generation of electron channeling patterns. Such patterns will be needed for fast crystal orientation analysis of ribbons using the scanning electron microscope.

1. Silicon Carbide Growth During Silicon Ribbon Pulling using Carbon Dies

During silicon ribbon growth small crystallites form in the orifice of the die. Such crystallites are also found floating in the meniscus at the top of the die. More or less frequently such a particle becomes attached to the silicon ribbon thus destroying the perfection of the ribbon. Similar observations are made on the outside of a carbon die in contact with the molten silicon. An accumulation of crystallites in the orifice of a carbon die is shown in Fig. 1a and on the outside of a die in Fig. 1b. Scanning electron micrographs of such small crystals scraped from the orifice and from the side of the die are shown in Figs. 2. These crystals appear equi-axed and expose mainly (111) and (100) surfaces. The morphology of these crystals is in agreement with the growth from a liquid phase by precipitation. Some of these crystals are found in clusters bonded to each other with a very limited area where their orientations are identical (Fig. 2d). It is obvious that beautiful small crystals are grown by this technique as an unwanted "side-product" of Si ribbon pulling.

Fig. 1a. Precipitates in carbon die orifice after silicon-ribbon growth.

Fig. 1b. Precipitates on side of carbon die after silicon-ribbon growth.

Fig. 2. Scanning electron micrograph of particles scraped from side of die (see Fig. 1b). (a) magnification 1.3 KX, (b) magnification 1.3 KX (sheet 1 of 2).

Fig. 2. Scanning electron micrograph of particles scraped from side of die (see Fig. 1b). (c) magnification 1.7 KX, (d) magnification 1.7 KX (sheet 2 of 2).

An optical micrograph of a particle embedded into the silicon ribbon during growth is shown in Fig. 3. Such particles have been found to destroy the crystal perfection of ribbons through the generation of stacking faults, twinning and slip. An example of this is shown in the x-ray topograph shown in Fig. 4. The morphology of such particles is readily recognized in SEM pictures shown in Figs. 5. For the SEM microscopy the specimen was lightly etched in a mixture of HNO_3 , $\text{HC}_2\text{H}_3\text{O}_2$, and HF . A complex conglomerate of crystals similar to the one shown in Figs. 2 is visible in the SEM micrograph of Fig. 5.

Identification of the crystal structure of such crystals, scraped from the die orifice and the die wall, was made through x-ray diffraction analysis. A similar analysis was made from the inclusions extruded from the silicon ribbons. The inclusions were removed from the ribbon by dissolving the surrounding silicon in an etch composed of 25 parts HNO_3 , 15 parts $\text{HC}_2\text{H}_3\text{O}_2$, and 15 parts HF . A few crystals were attached to a glass-rod and Debye-Scherrer diffraction patterns were obtained. The d-spacings measured from the films were checked against the A.S.T.M. card file. Identical patterns were obtained for scraped crystals and for inclusions. The crystals were identified as Beta Silicon Carbide. This zinc-blende type structure (cubic form) has a lattice constant of $a = 4.358$ Angstrom.

Fig. 3. Optical micrograph of particle embedded in ribbon (position indicated by arrow).

Fig. 4. X-ray topograph of ribbon showing defect generation due to embedded particles.

Fig. 5. Scanning electron micrograph of particle shown in Fig. 3. (a) 260X, (b) 1.25 KX.

The measurements are summarized in Table I.

TABLE I. Identification of Inclusions

<u>CRYSTAL</u>		<u>REFLECTION</u>	<u>ASTM CARD #1-119 BETA SiC</u>	
d	I _o	HKL	d	I/I ₁
2.51	S	111	2.51	100
2.18	M	200	2.17	20
1.54	M	220	1.54	63
1.315	M	311	1.31	50
1.27	W	222	1.26	5
		400	1.09	6
1.00	W	331	1.00	18
0.975	W	420	0.97	6
0.89	W	422	0.89	13
0.84	W	333,511	0.84	10

2. Identification of Surface Films

As-grown ribbons may show brownish-looking surface films. Such films were analyzed through electron diffraction. An electron diffraction pattern of such a film shows four broad rings and is given in Figs. 6. For evaluation of this pattern electron diffraction patterns were also produced from amorphous silicon generated on a silicon wafer through high dose argon implantation at 100 keV and also from SiO₂

Fig. 6a. Electron diffraction pattern, and its photodensitometer trace, of surface film.

Fig. 6b. Electron diffraction pattern, and its photodensitometer trace, of amorphous silicon produced by 100 keV argon implantation into silicon.

Fig. 6c. Electron diffraction pattern, and its photodensitometer trace, of SiO_2 thermally grown on silicon.

as-grown on a silicon wafer as obtained during oxidation. These diffraction patterns are also given in Figs. 6. Photo-densitometer traces of these diffraction patterns were used for evaluation of ring radii. All ring radii were calibrated through (220) and (111) silicon single crystal reflections obtained from diffraction patterns taken with the same camera length of the Hitachi HU200 microscope.

Table II summarizes the analytical results. It gives the ring radii as measured from the micro-densitometer traces of the diffraction patterns (Fig. 6) calibrated with a camera length $L = 115.64$ cm.

TABLE II. Ring Radii of Diffraction Patterns

Ribbon Surface Film	r_1	= (28.67 $\pm$ 0.5) mm
	r_2	= (36.5 $\pm$ 0.7) mm
	r_3	= (63.44 $\pm$ 1.3) mm
	r_4	= (94.4 $\pm$ 2.0) mm
Amorphous Si	r_{Si}	= (36.0 $\pm$ 0.7) mm
	r_{Si}	= (65.0 $\pm$ 1.3) mm
SiO ₂	r_{SiO_2}	= (29.0 $\pm$ 0.6) mm
	r_{SiO_2}	= (96.0 $\pm$ 2.0) mm

It can be seen that the rings numbered r_2 and r_3 of the diffraction patterns obtained from the surface film (Fig. 6a) match the ring pattern of the SiO_2 film (Fig. 6c) while the rings r_1 and r_4 of the surface film match the amorphous silicon rings.

According to a detailed study of silicon oxide films by Coleman and Thomas (Ref. 3) films of Si_xO_y have an average composition of Si and SiO_2 with y/x ranging between $2 \geq y/x > 0$. Based on such data we conclude that the brownish film on the ribbon surface is due to a silicon oxide film which decomposed (Ref. 4) according to $2 \text{SiO} \rightarrow \text{SiO}_2 + \text{Si}$.

RIBBON PERFECTION STUDIES

Twinning is a dominant mechanism during crystal growth of ribbons and of great influence on the perfection of the silicon ribbon. The nucleation frequency of twins is very high during the initial seeding operation and substantially lower during "steady-state" growth. The nucleation events leading to twinning can be categorized as follows:

- o Twinning during seeding.
- o Twinning at surface inclusions.
- o Spontaneous twinning.

All three cases are presently under investigation.

In the context of this work it will be important to evaluate surface orientation of ribbons fast and accurately. Such an evaluation can be very complex and very time-consuming because large sections of ribbons have to be investigated and the influence of seed orientation on twinning must be ascertained. This again calls for a variety of seeding experiments followed by ribbon growth until steady-state conditions are achieved and subsequent analysis of the material.

Visual inspection of ribbons is fast but obviously not sufficient - even if combined with optical microscopy of etched ribbon surfaces - if understanding of the complex twinning mechanism in such crystals is desired.

Up to date detailed studies of twinning phenomena in ribbon silicon have not been performed because this task is cumbersome. However, such an investigation is desirable because it would help in the understanding of ribbon growth.

Therefore, we have decided to perform this task and believe it can be done expediently using a "new" technique for

ribbon evaluation. This technique is based on the use of electron channeling patterns (ECP) for the measurement of surface orientation of crystals. In our laboratory this technique is now a viable tool because we were able to computer-generate maps of completely indexed ECP's of silicon crystals of any desired orientation.

Such maps were computer-generated for electron channeling patterns using a program that was previously written to plot Kikuchi patterns for transmission electron microscopy analysis (Ref. 5).

ECP's are formed in the scanning electron microscope by backscattered electrons of the electron beam probing the crystal surface. The technique can be used for precise orientation determination of crystals as small as 1 to 10 μm depending on the capability of the SEM. The backscattered electrons have the same energy as the incoming electrons. The maximum usable energy for our SEM is 30 keV. Therefore maps were plotted for this voltage. The maps were obtained for the (001), (011), and (111) pole in the center of the

projection. The following considerations were observed in generating the ECP's:

- o Detailed maps of the area covering 25 degrees of the three main poles are needed for ribbon analysis. Thus ECP lines up to the fourth order and up to $h^2 + k^2 + l^2 = 81$ were plotted. These maps are given in Figs. 7 to 9.
- o An overview around the center pole of up to ± 60 degrees is also desirable. Consequently, the center poles were plotted with ECP lines up to the fourth order and $h^2 + k^2 + l^2 = 49$. These patterns are given in Figs. 10 to 13.

Fig. 7. Computer-generated ECP: Si 30 kV (001); $x_0=y_0=12$, $R=32$, $RMN=4$, $SMSQ=9$.

Fig. 9. Computer-generated ECP: Si 30 kV (111); $x_0=y_0=12$, $R=32$, $RMN=4$, $SMSQ=9$.

Fig. 12. Computer-generated ECP: Si 30 kV (011); $x_0=y_0=12$, $R=11$, $RMN=4$, $SMSQ=7$.

REFERENCES

1. T. Ciszek and G. H. Schwuttke, Phys. Stat. Sol. (a) 27, 231, (1975).
2. J. C. Swartz, T. Surek, and B. Chalmers, J. Electron. Mater. 4, 255 (1975).
3. M. V. Coleman and D. J. Thomas, Phys. Stat. Sol. 22, 593 (1964).
4. E. Hengge, Topics in Current Chemistry, Silicon Chemistry II, Springer, New York, 1974, p.70.
5. H. Kappert, Technical Report No. 6, Chapter I, July 1975, ARPA Contract No. DAHC 15-72-C-0274.

ACKNOWLEDGMENT

Technical support was provided for by H. Ilker (electron microscopy). The SEM pictures were recorded by R. Dessauer.

Chapter 3

ECONOMIC EVALUATION AND COMPUTER-AIDED SIMULATION

A.Kran

INTRODUCTION

The general purpose of this effort is to develop an interactive computer model of photovoltaic energy conversion, which will aid the understanding of interactions between physical and economic variables associated with the growth of silicon to be used for low-cost solar-cell fabrication.

In any modeling effort, early interaction between the model builder and those who will subsequently utilize the results of his simulations is important. This interaction also aids in establishing credibility of the model, which cannot be effectively done without the users' understanding of how the model works and what problems it is trying to solve.

The first model of the simulation effort addresses silicon ribbon pulling and is described in this quarterly report. The specific objectives of our computer-aided modeling effort are as follows:

- o To understand the relative importance of crystal growth (i.e., growth rate) and subsequent solar-cell fabrication parameters (i.e., diffusion time, equipment cost) as they relate to product (i.e., solar cell) and energy cost.
- o To assign values to these parameters (i.e., capital equipment cost) and to be able to readily alter them, as more precise information is developed.
- o To undertake sensitivity studies in order to determine which parameters (i.e., crucible cost) play the more dominant parts in the economics of photovoltaic energy conversion.
- o To assess the impact of silicon (i.e., ribbon) technology improvements on the economic outlook for photovoltaics.
- o To model photovoltaic technology projections and to calculate future energy cost based upon achievement of these projections.

MATHEMATICAL MODEL

Since the computer model is coded in a scientific programming language (APL), a special effort has been made to also describe the model in conventional mathematical terms to facilitate better understanding. (Appendix I). For the same reason, the model structure is kept simple. It consists of 14 equations and 23 assigned process and economic parameters relating to the fabrication of silicon ribbon from poly crystalline material. These parameters are readily varied to answer "what if" type questions pertaining to future capability. Also, this module is classified as deterministic, meaning that it does not include random or probabilistic variables.

ECONOMIC BASELINE FOR RIBBON GROWTH

The model has been exercised to establish an economic baseline, or a preliminary analysis, of ribbon economics in view of today's crystal-growing technology. Three cases are presented, reflecting an optimistic, conservative, and pessimistic outlook. One production unit, consisting of a crystal puller plus the necessary manpower and raw materials to operate it over a 24-hour, 5-day week was used for this analysis. Ribbons are assumed to be grown on a continuous

basis at the given rates, with machine availability decreased from 100% to account for restarting the growth process after the crucible has been depleted of melt, or for random machine failure. The process variables are listed in Fig. 1.

The results of \$4369, \$8652, and \$18845/kwe at the material level shown in Fig. 2 are expectedly high and are calculated from current data. They simply represent one set of values, without taking anticipated improvements into consideration.

DATA FLOW AND PROCEDURE FOR MODEL USE

The data flow is shown in Fig. 3 and is best explained in conjunction with the procedure for utilizing the model. After system sign-on protocol, the defined functions (GVARS, LIST, CALC, DISPLAY) are loaded into the active workspace. The function GVARS assigns values to the process and economic parameters, which, after execution of GVARS, are available as global variables for subsequent calculation or mere listing, achieved through execution of LIST. Changes are readily made by either respecification or function edition.

RIBBON DATA

- 1 RIBBONS GROWN SIMULTANEOUSLY - 1 1 1
- 2 RIBBON WIDTH, CM - 3 2.5 2
- 3 RIBBON GROWTH RATE, M/HR - 1.8 1.5 1.2
- 4 RIBBON THICKNESS, MM - 0.2 0.3 0.4
- 5 YIELD OF GOOD RIBBON, PERCENT - 80 70 60

DIRECT COST

- 6 RIBBON FURNACE, DOLLARS - 25000 25000 25000
- 7 EQUIPMENT LIFE, YEARS - 7
- 8 INTEREST RATE, PERCENT - 8
- 9 EQUIPMENT AVAILABILITY, PERCENT - 75 70 65
- 10 PERSONNEL PER SHIFT
- 11 NO. OF SUPERVISORS - 0.05 AT A YEARLY RATE OF - 25000
- 12 NO. OF ENGINEERS - 0.1 AT A YEARLY RATE OF - 20000
- 13 NO. OF TECHNICIANS - 0.5 AT A YEARLY RATE OF - 10000
- 14 POLY SILICON COST, DOLS/KG - 65 65 65
- 15 POLY YIELD TO RIBBON, PERCENT - 85 80 75
- 16 SERVICES AND SUPPLIES
- 17 ONE CRUCIBLE PER DAY AT A COST OF - 30 DOLLARS
- 18 POWER COST AT - 0.05 DOLLARS PER KWH
- 19 ENERGY TO OPERATE EQUIPMENT - 20 KW

OVERHEAD - 50 PCT OF PERSONNEL + 10 PCT OF RAW MATL COST
G AND A - 10 PERCENT OF DIRECT COST + OVERHEAD

PROFIT BEFORE TAX, PERCENT - 10 OF DC + O/H + G + A

MISCELLANEOUS

- 20 WORKWEEK, HOURS - 120
- 21 CONVERSION EFFICIENCY, PERCENT - 9 8 7
- 22 ENERGY DENSITY AT AM1, KW/M SQ PEAK - 1

Fig. 1. Ribbon parameters and their assigned values.

Ribbons Grown Simultaneously	1.00	1.00	1.00
Ribbon width, cm	3.00	2.50	2.00
Avg Area Growth Rate, sq m/hour	0.03	0.02	0.01
Combined yield factor	0.68	0.56	0.45
Direct Cost in Dols/sq meter			
Equipment Capital Recovery	24.70	43.55	85.50
Personnel	127.31	224.49	440.71
Poly Silicon Cost	44.54	81.13	134.62
Services/Supplies	61.73	106.12	202.99
Subtotal:	258.29	455.30	863.82
Overhead Cost in Dols/sq meter	66.69	116.79	226.41
G&A Expenses in Dols/sq meter	32.50	57.21	109.02
Profit in Dollars/sq meter	35.75	62.93	119.93
Total Cost in Dols/sq meter	393.22	692.23	1319.18
Dollars per kw	4369.10	8652.84	18845.43

Fig. 2. Economics of silicon ribbon—one ribbon puller.

Fig. 3. Data flow model.

Calculation is accomplished by executing the function CALC, and results are displayed by executing DISPLAY.

The above can be further simplified by defining a function to handle this procedure.

LISTING OF APL FUNCTIONS

The APL functions are listed in Appendix II to further aid in the validation of the model, with computer code purposely written in transparent, easy-to-follow form.

MATHEMATICAL MODEL

1. ASSIGNED PARAMETERS

CC = CRUCIBLE COST, \$
 CH = ENERGY TO OPERATE EQUIPMENT, KW
 CP = POWER COST, \$/KWH
 DS = SILICON DENSITY, 2.33 G/CM³
 EC = CONVERSION EFFICIENCY, %
 ED = ENERGY DENSITY, PEAK AT AM1, KW/M²
 EP = EQUIPMENT PRICE, \$
 HW = WORK WEEK, HOURS
 FC = FACTOR, %
 IN = INTEREST, %
 LP = POLY SILICON COST, \$/KG
 LR = REMELTED MATERIAL, %
 LY = POLY YIELD TO RIBBON, %
 MA = MACHINE AVAILABILITY, %
 NU = NUMBER OF YEARS
 PE = ANNUAL SALARY OF ENGINEER, \$
 PS = ANNUAL SALARY OF SUPERVISOR, \$
 PT = ANNUAL SALARY OF TECHNICIAN, \$
 RG = RIBBON GROWTH RATE, M/HR
 RS = RIBBONS GROWN SIMULTANEOUSLY
 RT = RIBBON THICKNESS, MM
 RW = RIBBON WIDTH, CM
 RY = RIBBON GROWTH YIELD, %

2. CALCULATED PARAMETERS

AG = AREA GROWTH RATE, M^2/HR

CR = CAPITAL RECOVERY FACTOR

DC = DIRECT COST, $\$/M^2$

EC = CAPITAL EQUIPMENT COST, $\$/M^2$

GA = GENERAL & ADMINISTRATIVE COST, $\$/M^2$

LC = POLY SILICON COST, $\$/M^2$

NC = ENERGY COST AT MATERIAL LEVEL, $\$/KW$

NH = WORKING HOURS PER YEAR

PC = PERSONAL COST, $\$/M^2$

PR = PROFIT, $\$/M^2$

OH = OVERHEAD, $\$/M^2$

SS = SERVICES & SUPPLIES, $\$/M^2$

TO = COST OF TOTAL OPERATIONS, $\$/M^2$

YF = YIELD FACTOR

3. EQUATIONS

AREA GROWTH RATE (M²/HR)

$$\underline{AG} = RS \times RW \times RG \times RY \times MA$$

RS = RIBBONS GROWN SIMULTANEOUSLY

RW = RIBBON WIDTH, CM

RG = RIBBON GROWTH RATE, M/HR

RY = RIBBON GROWTH YIELD, %

MA = MACHINE AVAILABILITY, %

PERSONNEL COST (\$/M²)

$$\underline{PC} = ((PS \times FC) + (PE \times FC) + (PT \times FC)) \div (2000 \times \underline{AG})$$

PS = ANNUAL SALARY OF SUPERVISOR, \$

FC = AMOUNT OF TIME ASSIGNED, % FACTOR

PE = ANNUAL SALARY OF ENGINEER, \$

PT = ANNUAL SALARY OF TECHNICIAN, \$

AG = AREA GROWTH RATE, M²/HR

CAPITAL EQUIPMENT COST (\$/M²)

$$\underline{EC} = (\underline{EP} \times \underline{CR}) \div (\underline{AG} \times \underline{NH})$$

$\underline{EP}$ = EQUIPMENT PURCHASE PRICE, \$

$\underline{CR}$ = CAPITAL RECOVERY FACTOR

$\underline{AG}$ = AREA GROWTH RATE, M²/HR

$\underline{NH}$ = WORKING HOURS PER YEAR

CAPITAL RECOVERY FACTOR

$$\underline{CR} = \frac{\underline{IN} \times (1 + \underline{IN})^{\underline{NU}}}{(1 - \underline{IN})^{\underline{NU}} - 1}$$

$\underline{IN}$ = INTEREST, %

$\underline{NU}$ = NUMBER OF YEARS

POLY SILICON COST (\$/M²)

$$\underline{LC} = (LP \times DS \times RT) \div \underline{YF}$$

$$\underline{YF} = (RY \times LY) + ((1 - (RY \times LY)) \times LR)$$

LP = POLY SILICON COST, \$/KG

DS = SILICON DENSITY, 2.33×10^3 KG/M³

RT = RIBBON THICKNESS, MM

YF = YIELD FACTOR

RY = RIBBON YIELD, %

LY = POLY YIELD TO RIBBON, %

LR = REMELT MATERIAL, %

SERVICES & SUPPLIES (\$/M²)

$$\underline{SS} = ((CC \times 5) + (CP \times CH \times HW \times MA)) \div (\underline{AG} \times HW)$$

CC = CRUCIBLE COST, \$

CP = POWER COST, \$/KWH

CH = ENERGY TO OPERATE EQUIPMENT, KW

HW = WORK WEEK, HOURS

MA = MACHINE AVAILABILITY, %

AG = AREA GROWTH RATE, M²/HR

DIRECT COST (\$/M²)

$$\underline{DC} = \underline{EC} + \underline{PC} + \underline{LC} + \underline{SS}$$

$\underline{EC}$ = CAPITAL EQUIPMENT COST, \$/M²

$\underline{PC}$ = PERSONNEL COST, \$/M²

$\underline{LC}$ = POLY SILICON COST, \$/M²

$\underline{SS}$ = SERVICES AND SUPPLIES, \$/M²

OVERHEAD COST, \$/M²

$$\underline{OH} = (\underline{PC} \times FC) + (LP \times DS \times RT \times FC)$$

$\underline{PC}$ = PERSONNEL COST, \$/M²

FC = FACTOR, %

LP = POLY SILICON COST, \$/KG

DS = SILICON DENSITY, KG/M³

RT = RIBBON THICKNESS, M

GENERAL & ADMINISTRATIVE COST, \$/M²

$$\underline{GA} = (\underline{DC} + \underline{OH}) \times FC$$

$\underline{DC}$ = DIRECT COST, \$/M²

$\underline{OH}$ = OVERHEAD COST, \$/M²

FC = FACTOR, %

PROFIT, \$/M²

$$\underline{PR} = (\underline{DC} + \underline{OH} + \underline{GA}) \times FC$$

$\underline{DC}$ = DIRECT COST, \$/M²

$\underline{OH}$ = OVERHEAD COST, \$/M²

$\underline{GA}$ = GENERAL & ADMINISTRATIVE COST, \$/M²

FC = FACTOR, %

COST OF TOTAL OPERATIONS, \$/M²

$$\underline{TO} = \underline{DC} + \underline{OH} + \underline{GA} + \underline{PR}$$

$\underline{DC}$ = DIRECT COST, \$/M²

$\underline{OH}$ = OVERHEAD COST, \$/M²

$\underline{GA}$ = GENERAL & ADMINISTRATIVE COST, \$/M²

$\underline{PR}$ = PROFIT, \$/M²

ENERGY COST AT MATERIAL LEVEL, \$/KW

$$\underline{NC} = \underline{TO} \div (\underline{EC} \times \underline{ED})$$

$\underline{TO}$ = COST OF TOTAL OPERATIONS, \$/M²

$\underline{EC}$ = CONVERSION EFFICIENCY, %

$\underline{ED}$ = ENERGY DENSITY, PEAK AT AM1, KW/M²

LISTING OF APL FUNCTIONS

```

      VGVARS[ ]V
    ▽ GVAR$
[1]  CC+30
[2]  CH+20
[3]  CP+0.05
[4]  DS+2.33
[5]  EC+7.5
[6]  ED+1
[7]  EP+3p25000
[8]  FC+ 0.05 0.1 0.5 50 10 10 10
[9]  HW+120
[10] IN+8
[11] LP+3p65
[12] LR+0
[13] LY+3p80
[14] MA+70
[15] NU+7
[16] PE+20000
[17] PS+25000
[18] PT+10000
[19] RC+3p2.3
[20] RS+3p1
[21] RT+3p0.2
[22] RW+3p3
[23] RY+ 60 70 80
    ▽

```



```

VLIST[ ]V
V LIST;X
[1] X+125
[2] US1 ' LIST OF RIBBON PARAMETERS AND THEIR ASSIGNED VALUES'
[3] ' RIBBON DATA'
[4] X[1];' RIBBONS GROWN SIMULTANEOUSLY - ';RS
[5] X[2];' RIBBON WIDTH, CM - ';RW
[6] X[3];' RIBBON GROWTH RATE,M/HR - ';RG
[7] X[4];' RIBBON THICKNESS, MM - ';RT
[8] X[5];' YIELD OF GOOD RIBBON, PERCENT - ';RY
[9] ''
[10] ' DIRECT COST'
[11] X[6];' RIBBON FURNACE, DOLLARS - ';EP
[12] X[7];' EQUIPMENT LIFE, YEARS - ';NU
[13] X[8];' INTEREST RATE, PERCENT - ';IN
[14] X[9];' EQUIPMENT AVAILABILITY, PERCENT - ';MA
[15] X[10];' PERSONNEL PER SHIFT'
[16] X[11];' NO. OF SUPERVISORS - ';FC[1];' AT A YEARLY RATE OF - ';PS
[17] X[12];' NO. OF ENGINEERS - ';FC[2];' AT A YEARLY RATE OF - ';PE
[18] X[13];' NO. OF TECHNICIANS - ';FC[3];' AT A YEARLY RATE OF - ';PT
[19] X[14];' POLY SILICON COST, DOLS/KG - ';LP
[20] X[15];' POLY YIELD TO RIBBON,PERCENT - ';LY
[21] X[16];' SERVICES AND SUPPLIES'
[22] X[17];' ONE CRUCIBLE PER DAY AT A COST OF - ';CC;' DOLLARS'
[23] X[18];' POWER COST AT - ';CP;' DOLLARS PER KWH'
[24] X[19];' ENERGY TO OPERATE EQUIPMENT - ';CH;' KW'
[25] ''
[26] ' OVERHEAD - ';FC[4];' PCT OF PERSONNEL+ ';FC[5];' PCT OF RAW MATL COST
[27] ' G_AND_A - ';FC[6];' PERCENT OF DIRECT COST+OVERHEAD'
[28] ''
[29] ' PROFIT BEFORE TAX, PERCENT - ';FC[7];' OF DC+O/H+G&A'
[30] ''
[31] ' MISCELLANEOUS'
[32] X[20];' WORKWEEK, HOURS - ';HW
[33] X[21];' CONVERSION EFFICIENCY, PERCENT - ';EC
[34] X[22];' ENERGY DENSITY AT AM1,KW/M SQ PEAK - ';ED

```

V

```

VCALC[ ]V
V CALC;A;B;C;D;E;V;X;Y;Z
[1] Y+(V+50)*W+8*D+5
[2] C+3p0
[3] AG+RS*RW*RG*RY*MA*10*-6
[4] PC+((PS*FC[1])+(PE*FC[2])+(PT*FC[3]))/(Y*AG)
[5] EC+(X+AG*NH+V*HW)*EP*CR+CAP
[6] LC+(A+LP*2.33*RT)*YF+E+((1-(E+RY*LY*10*-4))*LR*10*-2)
[7] SS+((CC*D)+(CP*CH*HW*MA*0.01))/(AG*HW)
[8] DC+EC+PC+LC+SS
[9] QH+(PC*FC[4]*10*-2)+A*FC[5]*10*-2
[10] TO+B+PR+(FC[7]*10*-2)*B+DC+QH+GA+(DC+QH)*FC[6]*10*-2
[11] NC+TO/(EC*ED*10*-2)
[12] E+RS,C,RW,C,AG,C,YF,C,C,EC,PC,LC,SS,C,DC,C,QH,GA,PR,C,TO,C,NC
V

```

```

VCAP[ ]V
V Z+CAP;I;N
[1] I+IN*0.01
[2] N+NU
[3] Z+(I*((1+I)*N))/(((1+I)*N)-1)
V

```

```

VDISPLAY[ ]V
V DISPLAY;M;X
[1] M+ 23 30 p ' '
[2] X+(16),(8+115), 7 8
[3] ' ' 'ECONOMICS OF SILICON RIBBON + ONE RIBBON *ULLER'
[4] ' '
[5] '*RINTED FROM a.' 'RAN]S [ _ w[( ' ;PRINTED.
[6] ' '
[7] M[X[1];]+ 'RIBBONS VROWN [IMULTANEOUSLY '
[8] M[X[2];]+30p ' '
[9] M[X[3];]+ 'RIBBON WIDTH, CM '
[10] M[X[4];]+30p ' '
[11] M[X[5];]+ 'AVG AREA VROWTH RATE,SQ M/HOUR'
[12] M[X[6];]+30p ' '
[13] M[X[22];]+ 'COMBINED YIELD FACTOR '
[14] M[X[23];]+30p ' '
[15] M[X[7];]+ 'IRECT COST IN [OLS/SQ METER '
[16] M[X[8];]+ 'EQUIPMENT CAPITAL RECOVERY '
[17] M[X[9];]+ 'PERSONNEL '
[18] M[X[10];]+ 'OLY [ILICON COST '
[19] M[X[11];]+ 'ERVICES/[UPPLIES '
[20] M[X[12];]+30p ' '
[21] M[X[13];]+ 'UBTOTAL( '
[22] M[X[14];]+30p ' '
[23] M[X[15];]+ 'OVERHEAD COST IN [OLS/SQ METER'
[24] M[X[16];]+ 'V>a EXPENSES IN [OLS/SQ METER'
[25] M[X[17];]+ '*ROFIT IN [OLLARS/SQ METER '
[26] M[X[18];]+30p ' '
[27] M[X[19];]+ '~OTAL COST IN [OLS/SQ METER '
[28] M[X[20];]+30p ' '
[29] M[X[21];]+ 'OLLARS PER KW '
[30] M, 10 2 ZFT(23 3 pE)
V

```