1
2

DOE/PC/90295--T8

PYRITE SURFACE CHARACTERIZATION AND
CONTROL FOR ADVANCED FINE COAL
DESULFURIZATION TECHNOLOGIES

DEC 28 1992

DOE/PC/90295--T8

DE93 004946

DOE Grant No: DE-FG22-90PC90295

Eighth Quarterly Technical Progress Report
(from June 1, 1992 to August 31, 1992)

by

X. H. Wang (Principal Investigator)
J. W. Leonard and B.K. Parekh (Co-PIs).
A.M. Raichur and C.L. Jiang (Graduate Students)

Department of Mining Engineering and
Center for Applied Energy Research,
University of Kentucky,
Lexington, Kentucky 40506

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

Co
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

OCT 09 1991

TABLE OF CONTENTS

Summary	 3
Introduction	 4
Experimental Details	 4
Results	 5
I. Heterogeneity of Pyrite Surface Energetics	5
II. Surface Hydrophobicity of Pyrites Under Different Atmosphere	6
III. Effect of Flotation Gases on Coal Separation Efficiency	7
IV. Effect of Coal/Carbon Content on Pyrite Reactivity	7
Future Work	9
List of Figures	10-30

SUMMARY

This is the 8th quarterly technical progress report for the project entitled "Pyrite surface characterization and control for advanced fine coal desulfurization technologies", DE-FG22-90PC90295. The work presented in this report was performed from June 1, 1992 to August 31, 1992.

The objective of the project is to conduct extensive fundamental studies on the surface reactivity and surface hydrophobicity of coal-pyrites using various surface characterization techniques and to understand how the alteration of the coal-pyrite surface affects the efficiency of pyrite rejection in coal flotation. During this reporting period, the influence of the impurity content, particularly coal/carbon content, on the electrochemical oxidation of pyrite surfaces was investigated. The studies demonstrate that the coal/carbon content in coal-pyrite has a determining effect on the surface reactivity of pyrite. The oxidation behavior of high carbon-content coal-pyrite is completely different from that of purer coal-pyrite and ore-pyrite. The effects of flotation gases on the flotation behavior of coal and the surface hydrophobicity of various coal-pyrite were investigated. It was found from the lab-scale column flotation studies that among the various gases studied (air, oxygen, argon, nitrogen and carbon dioxide), carbon dioxide produced the best results with a combustible recovery of 90% and ash-content of less than 9 percent. Finally, the surface energetic studies revealed that the surfaces of pyrites and coals produced by wet grinding is more heterogenous than that prepared by dry grinding.

One of the graduate students, Mr. A.M. Raichur, who has been financially supported by this project, finished his M.S. degree in the end of July. His thesis entitled "Comparative studies of surface properties of pyrites from coal and ore sources" (140 pages) was evaluated as a high quality thesis by the examination committee.

INTRODUCTION

Surface-based physical separation techniques such as froth flotation and agglomeration have shown the potential for removing pyritic sulfur from coal. However, the efficiency of these techniques in rejecting pyrite from coal decreases significantly with ultrafine coal. The causes of the difficulties of pyrite separation from coal are complex and have not been systematically investigated. In addition to the superficial changes of pyrite surfaces, there are several other possible factors such as particle size, crystallinity, contamination, etc, that all can change the surface properties of pyrite. Therefore, it is of great significance to determine the role of each of the factors in coal-pyrite flotation.

The first series studies of this project showed that the electrochemical reactivity of coal-pyrite containing high carbon/coal content differs completely from that of ore-pyrite and less contaminated coal-pyrite [3rd and 4th quarterly reports and 1st annual report of this project]. We also found that the contact angle and floatability of pyrites can be significantly altered by grinding conditions, pretreatment, etc. Thus, in this reporting period, these aspects were investigated systematically.

EXPERIMENTAL

Column flotation was carried out using a laboratory scale conventional column cell of 1.6 liter capacity. An Upper Freeport coal sample was used in this study and the chemical analysis is presented in Table 1. The as-received coal was first wet ground in a rod mill for 30 minutes with about 50 percent solid content. The average product particle size was about 10 microns. Before column flotation, the slurry was diluted to about 8 percent solid concentration. Two liter of the slurry was first conditioned with 10 μ l MIBC (frother) and 12 μ l fuel oil (promoter) for five minutes. The flotation was then carried out at various flow rates between 500 to 2400 cc/min. When the pulp/froth interface reached a steady state, the float and tailing were sampled, filtered, dried and then analyzed for carbon, ash and sulfur content. All the flotation tests were conducted

at natural pH. The combustible recovery was calculated by the following formula:

$$R = \frac{\alpha - \gamma}{\beta - \gamma} \times 100$$

where

α = carbon content of feed coal

β = carbon content in clean coal

γ = carbon content in tailing

Details of other experimental techniques have been described in previous studies.

RESULTS

I. Heterogeneity of Pyrite Surface Energetics

Surface energy is an important parameter in characterizing the fundamental surface properties of a solid. The surface energy of a solid controls the flotation behavior of the solid. Recent important advances in this field have enabled us to quantitatively measure the surface energies of solids and the component terms of the total surface energy. In the previous reports, we have reported the results of the "critical surface tension of wetting" of the various coal-pyrite and the dispersion surface free energy, and acid-base surface free energy of pyrite under different solution conditions.

The film flotation method, developed by D.W. Fuerstenau and co-workers, is a simple way for estimating the critical surface tension of wetting, γ_c . Furthermore, the surface heterogeneity of the fine particles can be studied by examining the film flotation frequency distribution. Figure 1 shows the frequency distribution of the wetting surface tension for the Upper Freeport coal. It can be seen that the wetting surface tension of the coal is quite narrowly distributed in the range of 35-55 dyne/cm for the sample prepared dry grinding. This indicates that energetically, the coal surface has low heterogeneity. However, the results given in Figs. 2 and 3 show that the ore- and coal-pyrite surfaces

are very heterogenous, as the surface wetting tensions are distributed in a wide surface tension range . In comparison, the coal-pyrite KYPY is even more heterogenous than the ore-pyrite PUPY. Interestingly, for both coal- and ore-pyrite, when the particles were prepared by wet grinding, the surfaces of particles become more heterogenous; while surface "cleansing" by washing with EDTA or ultrasonication reduces the surface heterogeneity. This is probably due to the removal of iron hydroxides and oxides (layers, pits or tiny particles) formed during grinding from the surfaces, thereby exposing less heterogenous sulfur-enriched surface to solution.

II. Surface Hydrophobicity of Pyrites Under Different Atmosphere

Early studies of this project showed that when the surfaces of pyrite are exposed to air and water, oxidation takes places rapidly. No equilibrium contact angle could be obtained if the measurements were made in air using the sessile drop method. In order to study the surface hydrophobicity of pyrite in air and under nitrogen, a method was developed, by which the contact angles of freshly prepared surfaces can be estimated by extrapolating the contact time to zero. Using this method, the contact angles of different pyrites and coal were determined as a function of solution pH.

Figure 4 shows the contact angle as a function of pH for different pyrites. For comparison, the contact angle of the Illinois coal sample is also presented. It can be seen that all the coal-pyrites exhibit much higher contact angles than the ore-pyrites at the all pH's. While the contact angle of the Illinois No.6 coal remains almost constant in the whole pH range, the contact angles of all the pyrites vary with the solution pH and show maxima in the neutral pH range. Similar results were obtained under a nitrogen atmosphere, as shown in Fig.5. However, the contact angles measured under nitrogen are lower than that measured in air.

Since the equilibrium contact angles of pyrite cannot be easily accessed by measuring contact angle under nitrogen or in air, a more reliable method was used in

which the contact angle of a water droplet was measured under hexane. It was found that under hexane, the contact angle does not change even when the contact time was over one hour. Figure 6 presents the contact angles of various pyrites and the Illinois No.6 coal as a function of solution pH. It can be seen that the coal sample exhibits a much higher contact angle than all the pyrites. Coal-pyrites show higher contact angles than ore-pyrite. Furthermore, the contact angles of the pyrites change with the solution pH and shows a maximum in the neutral pH range.

III. Effect of Flotation Gases on Coal Separation Efficiency

It was found from our early studies that in a carbon dioxide saturated solution, the surface hydrophobicity of pyrite decreases, while in oxygen/air-saturated solutions, the contact angle increases with increasing time. The results suggest that using carbon dioxide may improve the separation efficiency. Thus, a series of lab-scale column flotation studies were carried out to examine the effects of flotation gases on the flotation behavior of coal and coal-pyrites.

The flotation results with compressed air, nitrogen, argon and carbon dioxide as the flotation gas are shown in Figs. 7-10, respectively. When compressed air, nitrogen or argon was used as the flotation gases, the combustible recovery was low at low gas flow rates. The combustible recovery increases with increasing gas flow rate. However, the ash-content also increases significantly, from 8 percent at 500 cc/min to 16 percent at 2400 cc/min. In comparison, when carbon dioxide is used as the flotation gas, the flow rate essentially has no effect on the combustible recovery and the ash-content in the concentrate. At a flow rate of 500 cc/min, a combustible recovery of about 90 percent was obtained with less than 9 percent ash-content. In another series of studies, the effect of flotation gases on the pyrite rejection efficiency was studied with a synthetic coal/pyrite mixture. The results showed that when the combustible recovery was kept the same, the pyrite rejection was much higher in using carbon dioxide as the flotation gas than using other gases.

IV. Effect of Coal/Carbon Content on Electrochemical Oxidation

Our first series comparative studies of pyrites from ore and coal sources demonstrated that the electrochemical reactivity of pyrite changes abruptly when the pyrite contains high coal/carbon content ($>3\%$). For example, the Illinois coal-pyrite (ICPY), which contains 0.8 percent carbon, behaves almost identical to the pure ore-pyrites in the electrochemical oxidation/reduction processes. However, with coal-pyrite selected from Pittsburgh No.8 and Kentucky No.9 coal seams, which contains carbon content of 3-4 percent, the current density was very high but no characteristic redox peaks were observed. Thus, it is of great importance to conduct more systematic studies.

Since besides carbon and other impurity content, there are many other factors that can change the electrochemical reactivity of pyrites, such as source, crystallinity, composition deviation, etc. In order to reduce other possible influential factors, we have selected a large polycrystalline Kentucky No.9 coal-pyrite. Physically, portion of this pyrite showed the same crystal faces and appearance as the common ore-pyrite, while the rest part was adhered by some coal particles. After removing the coal particle by hand, the crystal was cut into two large pieces along the "boundary" using a diamond saw. Each piece was then cut again, and two cubic specimen (5x5 mm) was obtained from the core part. The specimen were used to prepare two electrodes. For clarity, the electrode made from purer part is denoted as KYPY1, while the electrode made from the other part of the crystal is named as KYPY2. The electrochemical reactivity was then studied under various solution conditions. We here report the results obtained at two typical pH's and compare them with the other high coal-content KYPY electrode and pure ore-pyrite electrodes.

Figures 11-14 present the cyclic voltammograms of PUPY, KYPY1, KYPY2 and KYPY at pH=5, respectively. It can be seen that the cyclic voltammograms of KYPY1 under both stationary and rotating conditions closely resemble that of the PUPY's. However, the voltammograms of KYPY2 are remarkably different from that of KYPY1 and

PUPY. Although they are more like that of KYPY's, there are differences in two aspects: (1) the current density of KYPY2 is much lower than that of KYPY; (2) the rotation-dependence phenomena are still visible with the KYPY2. Figures 15-18 show the cyclic voltammograms of SPPY, KYPY1, KYPY2 and KYPY in highly alkaline solutions (pH=11.0), respectively. Like in acidic solutions, KYPY1 is very much like the ore-pyrite (SPPY), while KYPY2 is between the pure ore-pyrite and high carbon-content coal-pyrite (KYPY). As can be seen, the rotation dependence can still be observed with KYPY2.

These results demonstrate that the content of carbonaceous materials has a determining effect on the surface reactivity of pyrite. Above a certain limit, the surface properties of pyrite changes abruptly. Furthermore, even within the same pyrite crystal, the content of the carbonaceous materials can vary significantly at different part, thus, the surface properties can be remarkably different.

PLAN FOR FUTURE WORK

The flotation behavior of coal- and ore-pyrite under various chemical conditions will be investigated in detail. The effects of surface alteration by different means on the floatability of pyrite will be examined. Effective coal-pyrite separation techniques are being studied.

Table 1 Chemical analysis of As-received Upper Freeport coal
used in column flotation tests.

Analysis	Weight Percent
Moisture	1.3
Ash	25.18
Volatile Matter	20.6
Fixed Carbon	52.9
Total Sulfur	3.22
Pyritic Sulfur	2.00
Sulfate Sulfur	0.33
Organic Sulfur	0.89

Fig.1 Distribution of surface wetting energy of Upper Freeport Coal.
(a) prepared by dry grinding;
(b) prepared by wet grinding, followed by ultrasonic surface cleaning.

Fig.2 Surface wetting energy distribution of the ore-pyrite PUPY.

(a) prepared by dry grinding;

(b) prepared by wet grinding;

(c) prepared by wet grinding, following by surface cleaning with EDTA.

Fig.3 Surface wetting energy distribution of the coal-pyrite KYPY.

- (a) prepared by dry grinding;
- (b) prepared by wet grinding;
- (c) prepared by wet grinding, followed by ultrasonic surface cleaning;

Fig.4 Comparison of the contact angles of water droplets on freshly prepared pyrite surfaces measured in air under different solution pH's.

Fig.5 Comparison of the contact angles of water droplets on freshly prepared pyrite surfaces measured under a nitrogen atmosphere under different solution pH's.

Fig.6 Comparison of contact angles of water droplets on freshly prepared pyrite and coal surfaces measured under hexane at different solution pH's.

Fig.7 Effect of air flow rate on the combustible recovery and ash content of fine Upper Freeport coal in column flotation with compressed air as flotation gas

Fig.8 Effect of flow rate on the combustible recovery and ash content of fine Upper Freeport coal in column flotation with nitrogen as flotation gas.

Fig.9 Effect of flow rate of argon on the combustible recovery and ash content of fine Upper Freeport coal in column flotation with argon as flotation gas

Fig.10 Effect of flow rate of carbon dioxide on the combustible and ash content of fine Upper Freeport coal in column flotation with carbon dioxide as flotation gas.

Fig.11 Cyclic voltammograms of the ore-pyrite PUPY at pH=5.6.

Fig.12 Cyclic voltammograms of the "purer" coal-pyrite KYPY1 at pH=5.0

Fig.13 Cyclic voltammograms of moderately coal-contaminated coal-pyrite KYPY2 at pH=5.0

Fig.14 Cyclic voltammograms of highly coal-contaminated coal-pyrite (3.8% C) KYPY at pH=5.6.

Fig.15 Cyclic voltammograms of the ore-pyrite SPPY at pH=10.0

Fig.16 Cyclic voltammograms of the "pure" coal-pyrite KYPY1 at pH=11.

Fig.17 Cyclic voltammograms of the "moderately" coal-contaminated coal-pyrite KYPY2 at pH = 11.

Fig.18 Cyclic voltammograms of the highly coal-contaminated coal-pyrite KYPY at pH=10.0

**DATE
FILMED
02/02/93**