THE EFFECT OF CHEMICAL ADDITIVES ON THE SYNTHESIS OF ETHANOL

DOE/PC/79923--T17

DE92 018898

Technical Progress Report 10

Grant No. DE-FG22-87PC79923

Dec. 16, 1989

-

March 15, 1990

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

by

Steven S.C. Chuang

Department of Chemical Engineering

University of Akron

Akron, OH 44325 U.S.A.

Date of Submission: July, 1990

US/DOE Patent Clearance is not required prior to the publication of this document.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY

The objective of this research is to elucidate the role of various chemical additives on ethanol synthesis over Rh- and Ni-based catalysts. Chemical additives used for this study will include S, P, Ag, Cu, Mn, and Na which have different electronegativities. The effect of additives on the surface state of the catalysts, heat of adsorption of reactant molecules, reaction intermediates, reaction pathways, reaction kinetics, and product distributions is/will be investigated by a series of experimental studies of NO adsorption, reaction probing, steady state rate measurement, and transient kinetic study.

A better understanding of the role of additive on the synthesis reaction may allow us to use chemical additives to manipulate the catalytic properties of Rh- and Ni-based catalysts for producing high yields of ethanol from syngas.

RESULT TO DATE

During the first quarter of 1990, the CO insertion activity of sulfided Group VIII metals was studied by using ethylene hydroformylation as a probe reaction.

ABSTRACT

NiS and sulfided group VIII metals including Ni, Co, Fe, Ru, Ir, and Os have been found to exhibit hydroformylation activities in 150 - 300 °C and 10 atm.

Key word listing

Hydroformylation, Aldehyde, Synthesis Gas (CO/ H₂)

Ethylene, Propionaldehyde, Sulfided Group VIII Metals, NiS

INTRODUCTION

Hydroformylation, a reaction of olefin with carbon monoxide and hydrogen for the production of aldehydes and alcohols, is well known to be a homogeneously catalyzed reaction [1-5]. Metal carbonyls and their modified forms have long been employed for the commercial hydroformylation process. The major disadvantage of the homogeneous process is the expensive separation steps after hydroformylation stage for catalyst recovery and product purification [5-6]. To avoid the separation steps, various heterogeneous hydroformylation catalysts have been prepared by the use of polymer or oxides for anchoring metal complex catalyst as well as mixed metal oxides as catalysts. However, most of these catalysts exhibit poor thermal stability and activity [6-7].

Supported Rh has been found to be one of the most active catalyst for heterogeneous hydroformylation [8,9]. Recent studies have shown that H_2S fails to poison hydroformylation over Rh/SiO₂ [10,11] while H_2S enhances hydroformylation on Ni/SiO₂ [12]. These observations have led to investigation of hydroformylation on other sulfided Group VIII metals. We report here a new finding that NiS, sulfided Co, Fe, Ru, Ir, and Os exhibit a wide range of hydroformylation activities. Results of hydroformylation on the sulfided Rh and Ni are also included for comparison.

EXPERIMENTAL

Supported Ni, Co, Ru, Rh, Os, and Ir catalysts were prepared by impregnation of SiO₂ (large pore, Strem Chemicals) with Ni(NO₃)₂ · 6H₂O, Co(NO₃)₂ · 6H₂O, RuCl₃ · 3H₂O, RhCl₃ · 3H₂O, H₂OsCl₆ · 6H₂O, and IrCl₃ · 3H₂O, respectively. Fe/SiO₂ was prepared by precipitating FeCl₃ solution with Na₂CO₃. The precipitate was filtered and washed with water at room temperature. Following the impregnation or precipitation, the catalysts were dried at 30 °C and reduced in flowing hydrogen at 400 °C for 16 hrs. The metal crystallite size was determined by X ray diffraction-line broadening. The resulting catalysts were sulfided by 1000 ppm H₂S in H₂ at 400 °C. The bulk ratio of sulfur to metal was determined by energy-dispersive spectroscopy. It was found that sulfidation with either 240 or 400 °C resulted in the catalysts exhibiting the same activity and selectivity.

Ethylene hydroformylation (CO:H₂:C₂H₄ = 1:1:1) over sulfided metals was studied in a differential reactor at 10 atm and 150 - 300 °C. The reaction product was analyzed by a gas chromatograph using a 6 ft Porapak PS column in series with 6 ft Porapak QS column. The combination of these two columns permits a good on-line separation of all C₁-C₇ hydrocarbons, aldehyde, and alcohols. Due to the heterogeneity of the surface of sulfided metals and the lack of information on the site for the reaction, the rate will be reported on the basis of mol/kg hr. rather than turnover number.

RESULTS AND DISCUSSION

Table 1 shows the rate of ethylene conversion and product selectivity for ethylene hydroformylation over sulfided metals. Although all the sulfided metals were sulfided under the same condition, the ratio of sulfur to metal for the sulfided metals appears to depend on the type of metals and their thermodynamic properties [13,14]. It would be very difficult to maintain the same ratio of sulfur to metal for all the catalysts in this study. The sulfur content of the catalyst remains about the same during the entire course of reaction studies.

Ethane and propionaldehyde are major products while CH_4 , C_3+ hydrocarbons, and $\text{C}_3\text{H}_7\text{OH}$ are minor products. Variation of the H_2S concentration in the reactant stream from 0 - 1000 ppm did not affect the catalyst activity and selectivity. The rates of formation of CH_4 and C_3+ hydrocarbons in ethylene hydroformylation are comparable to those from CO hydrogenation on the sulfided metals indicating that the formation of these minor products from CO hydrogenation were inhibited by sulfur [15,16]. The inability of sulfur to completely poison ethylene hydrogenation is not surprising since most transition metal sulfides are active for olefin hydrogenation in 120 - 400 °C [17].

Variation of reaction temperature and pressure showed that decreasing reaction temperature shifted the product selectivity toward propionaldehyde for all the sulfided catalysts; while decreasing the reaction pressure enhanced the ethane selectivity. Infrared studies of CO adsorption on the sulfided Ni, Rh, and Ru

showed that sulfidation led the disruption of bridge-CO site resulting in the formation isolated atom site for linearly adsorbed CO [15]. It is likely that the isolated atom site is responsible for the hydroformylation reaction.

Comparison of the product selectivity in Table 1 shows that the sulfided Ni is the most selective catalyst for ethylene hydroformylation. Thus, we further investigated hydroformylation activity of NiS (Johnson Matthey). The results are presented in Table 2. Propionaldehyde selectivity on NiS is significantly higher than those on the sulfided metals. In contrast to sulfided Ni, methane is the major product at temperature below 210 °C; increasing reaction temperature from 210 to 288 °C shifts the selectivity toward propionaldehyde.

MoS₂ modified with Li, K, and Mg has been reported to exhibit hydroformylation activity [18]. However, pure MoS₂ showed only hydrogenation activity at 10 atm and 210 - 300 °C. Studies on other metal sulfides such as MnS and CrS also revealed that these sulfides are inactive for hydroformylation but active for hydrogenation at 10 atm and 210 - 300 °C [19].

In conclusion, sulfided Group VIII metals exhibit hydroformylation activities. Sulfided Ni appears to be the most active sulfide catalyst for the reaction.

ACKNOWLEDGEMENT

Funding for this research was provided by U. S. Department of Energy under DE-FG-22-87PC79923.

REFERENCES

1. F. A. Cotton and G. Wilkson, *Advanced Organic Chemistry*, 5th ed. Wiley, 1988.
2. I. Wender and P. Pino (Editors), *Organic Synthesis via Metal Carbonyls*, Vol. 2, Wiley, New York, 1977.
3. C. Masters, *Homogeneous Transition-Metal Catalysis - a Gentle Art*, Chapman and Hall, New York and London, 1981.
4. G. W. Parashall, *Homogeneous Catalysis - The Applications and Chemistry of Catalysis by Soluble Transition Metal Complexes*, Wiley, New York, 1981.
5. R. A. Sheldon, *Chemicals from Synthesis Gas*, D. Reidel Pub., Boston, 1983.
6. J. Fable (Editor), *New Syntheses with Carbon Monoxide*, Springer-Verlag, Berlin-Heidelberg-New York, 1980.
7. M. W. Blaskie, J. R. Fox, and F. Aesa, U. S. Patent 4,361,711, 1980.
8. M. Ichikawa, *J. Catal.* 56 (1979) 127.
- 9.. W. M. H. Sachtler and M. Ichikawa, *J. Phys. Chem.*, 90 (1986) 4752.
10. Y. Konishi, M. Ichikawa and W. M. H. Sachtler, *J. Phys. Chem.*, 91 (1987) 6286.
11. S. S. C. Chuang and S. I. Pien, *J. Mol. Catal.*, 55 (1989) 12.
12. S. I. Pien, Ph.D. Preliminary Results, Univ. of Akron, 1990.
13. C. H. Bartholomew, P. K., Agrawal, P. K., and J. R. Katzer, *Advances in Catalysis*, Vol. 31 (1982) 135.
14. J. Qudar and H. Wise (Editors), *Deactivation and Posioning of Catalysts*, Marcel Dekker, New York, 1985.
15. S. S. C. Chuang, S. I. Pien, and C. Sze, *J. Catal.* in press
16. A. G. Dastidar, M. S. Thesis, University of Akron, 1990.
17. P. C. H. Mitchell, in C. Kemball (Editor), *Catalysis, Specialist Periodic Report*, The Chemical Society, London 1977, Vol. 1, p. 204
18. N. E. Kinkade, *Europ. Patent* 0 149 256, 1985.
19. Unpublished results.

Table 1 Ethylene Hydroformylation on Sulfided Metals

Catalyst (the ratio of Sulfur to Metal)	Metal Loading (wt%)	Rate of C ₂ H ₄ Convrsion (mol/kg hr)	Product Selectivity				
			CH ₄	C ₃ +	C ₂ H ₄ (mol %)	C ₂ H ₅ CHO	C ₃ H ₇ OH
S-Fe 0.21	10	0.31	0.9	1	80.1	18	0
S-Co 0.3	5	9.2	0.2	0.3	83	16.5	0
S-Ni 0.46	15	4.5	0.4	0.01	59	37.1	1.5
S-Ru 0.12	3	0.65	3	1.3	84	11	0.7
S-Rh 0.14	3	52.4	1	0	68	29.3	1.7
S-Os 0.11	3	1.1	0	0	94	6	0
S-Ir 0.12	3	10.1	2	0	88	10	0

Reaction Condition: 10 atm, 270 °C

Product Selectivity = $\frac{\text{Rate of Formation of a Specific Product}}{\text{Rate of Formation of all Products}}$

Table 2 Ethylene Hydroformylation on NiS

Reaction Temperature (°C)	Product Distribution		
	CH ₄	C ₂ H ₄ (mol %)	C ₂ H ₅ CHO
210	47.1	12.3 (0.02) ^a	40.5 (0.066)
230	12.2	3.7 (0.025) ^a	82.9 (0.53)
275	8.9	4.8 (0.06) ^a	87.6 (1.07)
288	9.4	5.6 (0.054) ^a	84.6 (0.82)

Reaction Pressure: 10 atm

a: rate of product formation in mol./kg hr.

END

**DATE
FILMED**

9/04/92