Technical Progress Report

to

United States Department of Energy
Pittsburgh Energy Technology Center

Attention: Mr. James D. Hickerson, Program Officer
David Hunter, Contract Specialist
Richard Rogus, Contract Officer

MOLTEN IRON OXYSULFIDE AS A SUPERIOR SULFUR SORBENT

DOE/DE-FG22-89PC89778

by

Malcolm T. Hepworth
Principal Investigator

Period Covered:
~~Research Quarter~~
June 1 - August 31, 1990

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT*

Slagging combustors with injected lime or limestone are being considered as replacements for conventional coal burners. They have advantages in that they can be staged to reduce NO_x and SO_x emissions. Iron oxide, as an alternative to lime or limestone may be effective not only as a desulfurizing agent, but under the right conditions of oxygen potential and after combination with sulfur, the reaction products of coal gases with iron oxide can act as a flux to produce a fluid phase. The thermodynamic conditions for determining the most effective operating conditions of the first stage of a combustor are calculated for several Illinois coals. These conditions include contact of the gas with the phase combinations: CaO/CaSO_4 , CaO/CaS , and $\text{Fe}/\text{FeO}/\text{Liquid}$ for the temperature range 950° to 1300°C . In the latter system, the minimum dosage of iron required at equilibrium and the calculated maximum percent sulfur removal are reported. Also given are the expected pounds of SO_2 per million Btu of heat evolution calculated for complete combustion. The calculations indicate that for the Fe-O-S system, higher temperatures give better results approaching 96 percent sulfur removal from a coal containing 4.2% sulfur. For this example, the stack gas emerging from the second stage of combustion under stoichiometric conditions would contain 0.36 pounds of SO_2 per million BTU's of heat generated. The temperature limits of the sulfate and sulfide forming reactions are defined.

*Underlined are key words.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

INTRODUCTION

In this quarter, a paper was written for submission to the Journal Energy and Fuels. The text which follows is the content of that paper with additional information which is presented in the Appendix to this report.

Development in slagging combustors for utility coal combustion is being driven by several factors:

- * Removal of coal combustion residues as dense constituents at the source of combustion to reduce ash transfer to heat exchangers and down-stream fly ash capture devices,
- * Incorporation of staged-combustion to minimize NO_x emissions,
- * Utilization of added sorbents to reduce SO_x emissions,
- * Capability of operation at elevated pressures suitable for combined cycle operation.

A recent survey¹ indicated that lime or limestone was currently the only sorbent being injected in slagging utility burners for those systems close to, or currently undergoing commercial development. Some researchers, notably Avco, Inc.² have experimented with added iron as a sorbent material with initial success. The results of some preliminary studies by AMAX, Inc. on iron oxide additions to the reducing stage of a small coal burner was reported³ to result in up to 90 percent sulfur removal into a compact residue. This residue appeared to be inert with respect to sulfur re-emission when exposed to moisture. Avco confirm these preliminary findings in experiments conducted late in 1989; however, they were not able to achieve the high degrees of desulfurization reported in the AMAX study.

This paper is written entirely from a thermodynamic point of view. It compares the degree of desulfurization which can be achieved using an iron system with a calcium-based system operating under both reducing conditions (to produce calcium sulfide) and oxidizing conditions (to produce calcium sulfate). For this study calculations were made on several Illinois coals as fuels. They are restricted to those sulfur potentials which occur for the four phase equilibrium: gas + iron + wustite (FeO) + liquid iron oxysulfide. In a future study, the calculations reported in this paper will be extended to the iron-oxygen-sulfur system where only two phases are present: gas and the oxysulfide liquid.

Iron may be considered a potential alternative to lime as a sorbent for several reasons:

- * It forms a series of low-melting-point liquid solutions with iron and oxygen under reducing conditions. These liquids should be highly reactive with respect to adsorption of sulfur in the gases which they contact. Because they are liquids rather than solids, good internal

mixing under the high shear conditions of cyclonic burners should enhance the kinetics of absorption and also achieve sulfur adsorption closer to the predicted stoichiometry than would occur with a solid sorbent.

- * However, lime, being a solid, has been shown to require from two-to-five times the stoichiometric ratio of calcium-to-sulfur⁴ in order to produce a high degree of desulfurization.
- * Iron in the form of taconite concentrates (magnetite) is cost-competitive with lime at locations close to Great Lakes' ports (approximately \$30/short ton, FOB).

THERMODYNAMIC ANALYSIS

Although experimental work is presently in progress to determine the phase equilibria in the liquid phase for the iron oxysulfide system, this information has not been completed, and therefore, for this reporting, effort is directed towards the thermodynamics of the equilibria described below.

In the thermodynamic analysis the method of calculation will be defined for determining the gas phase compositions which can be expected under equilibrium conditions upon burning several types of coals. Initial examples will be on an Illinois #2 Coal (Colchester). The three systems CaO/CaSO₄, CaO/CaS, and Fe/FeO/Liquid will be examined. Finally the calculations will be extended to five Illinois #6 coals.

Method of Calculation:

The method of calculation was via an iterative approach for complex equilibria as detailed by Y. K. Rao⁵. The elements which are considered in the calculations are N, C, O, H, and S. These elements along with the predominant gas species of N₂, CO, CO₂, H₂O, H₂, H₂S, S₂, COS, SO, SO₃, SO, and O₂, are incorporated in the calculations to yield seven independent equations for the equilibria plus five additional equations for the mass balances. The relevant equations are as follows:

$$2H_2 + S_2 = 2H_2S \quad K_3 = \frac{P_{H_2S}^2}{P_{H_2}^2 \cdot P_{S_2}} \quad (3)$$

$$S_2 + 2O_2 = 2SO_2 \quad K_4 = \frac{P_{SO_2}^2}{P_{S_2} \cdot P_{O_2}^2} \quad (4)$$

$$2SO_2 + O_2 = 2SO_3 \quad K_5 = \frac{P_{SO_3}^2}{P_{SO_2}^2 \cdot P_{O_2}} \quad (5)$$

$$2CO + S_2 = 2COS \quad K_6 = \frac{P_{COS}^2}{P_{CO}^2 \cdot P_{S_2}} \quad (6)$$

$$S_2 + O_2 = 2SO \quad K_7 = \frac{P_{SO}^2}{P_{S_2} \cdot P_{O_2}} \quad (7)$$

$$n_C = n_{CO} + n_{CO_2} + n_{COS} \quad (8)$$

$$n_S = n_{H_2S} + n_{SO_2} + n_{SO_3} + 2n_{S_2} + n_{COS} + n_{SO} \quad (9)$$

$$n_H = 2n_{H_2O} + 2n_{H_2} + 2n_{H_2S} \quad (10)$$

$$n_O = n_{CO} + 2n_{CO_2} + 2n_{C_2} + n_{COS} + n_{SO} + 2n_{SO_2} + 3n_{SO_3} \quad (11)$$

$$n_N = 2n_{N_2} \quad (12)$$

Upon solving the twelve equations, the composition of the gas in equilibrium with the solid phases can be determined. An iterative computer program was developed which permits coal assays to be entered as variables as well as

temperature of combustion, total pressure, and moisture content. The program has three branches for the following equilibria: CaS/CaO , CaSO_4/CaO , and $\text{Fe}/\text{FeO}/\text{Liquid}$. The detailed program was reported in the previous quarterly report⁶.

Analysis of Lime-Based Systems:

A Western Illinois #2 Coal (Colchester), designated IBC-(Illinois Basin Coal) 102⁷ having the analysis given below was employed for calculations which follow in this and the next major heading. The analyses which were incorporated into the calculations are for 100g of dry coal plus 14.2 g moisture:

<u>Constituent</u>	<u>% by Wt.</u>
Carbon	73.92
Hydrogen	5.29
Nitrogen	1.52
Total sulfur	3.29
Oxygen	9.02 (not included in ash)
Ash	<u>6.9</u>
Total	100.0 (dry basis)
Moisture	14.2
BTU/lb	13,582

Data were taken from Kubaschewski and Alcock⁸ for the thermodynamics of the gas phase interactions and for the stabilities of the calcium compounds.

The results of these calculations are shown in Figure 1 for the system Ca-S-O. This figure is a predominance diagram in which the equilibrium phase regions are designated on a logarithmic plot of partial pressures of $\text{S}_2(\text{g})$ in atmospheres on the ordinate and log oxygen partial pressure as a measure of the chemical potential of oxygen on the abscissa. The solid lines represent conditions at 1000° C and the dashed lines at 1300° C, respectively. As is expected, calcium sulfide is oxidized upon increasing the oxygen potential to the sulfate form and can only be maintained under the reducing conditions shown. As temperature is increased the transition from sulfide to sulfate occurs under more oxidizing conditions. Also as temperature is increased, the equilibrium between sulfide and oxide occurs at lower sulfur pressures in the equilibrium between CaS and CaO; however, the higher sulfur pressures occur at higher temperatures in the equilibrium between CaO and CaSO_4 phases.

Calcium sulfide system:- Information from use of the interactive program on coal IBC-102 as applied to the $\text{CaO}/\text{CaS}/\text{gas}$ system are shown in Figure 2. This plot shows the theoretical dosage of lime required and the calculated equilibrium sulfur concentration reported as pounds of SO_2 per million BTU versus temperature. The

sulfur concentration is based upon the concentration which would be present at conditions of stoichiometric combustion. This basis is taken for this figure and for 9, 11, and 12. For Figure 2, the partial pressure of oxygen was arbitrarily taken at 10^{-12} atmospheres with a total gas pressure of 1 atmosphere. Conditions are for the reducing stage of a two-stage combustor. This Figure substantiates the result shown in Figure 1; that is, high temperatures for the calcium sulfide system yield a higher degree of desulfurization. The upper limit of stability of calcium sulfide is well above 2000°C.

Calcium sulfate system:- The converse is true for lime used as a sorbent under oxidizing conditions; i. e., with calcium sulfate as the product of reaction. Figure 3 shows that for temperatures much above 1150° C, the sulfur pressure rises rapidly. The conditions chosen were for an oxygen pressure of 0.05 atmospheres, or a slight excess of oxygen over stoichiometric requirements. In Figures 2 and 3 the theoretical dosage of lime is also plotted. As a greater proportion of the sulfur reacts with lime, the dosage of lime required, of course, increases (Fig 2); whereas, the converse is true for Figure 3 where lime becomes less effective as a desulfurizer at increasing temperatures.

Analysis of Iron-Based System: Equilibrium of Fe/FeO/Liquid/Gas:

Again the analyses for coal: IBC-102 was used as the input to another branch of the interactive computer program for calculating the gas compositions in equilibrium with the phases Fe/FeO/L/G. The iron oxygen-sulfur systems incorporates data from Darken and Gurry⁹, Bog and Rosenqvist¹⁰, Rosenqvist and Hartvig¹¹, and Burgmann et al.¹² as reported by Turkdogan and Kor.¹³

Some of the interesting features of the Fe-O-S system are shown in Figure 4. This figure is a ternary projection of the liquidus surfaces showing the phase pyrrhotite (FeS) at the lower right hand corner. The liquid phase is seen to be in the thermal "trough" with a ternary eutectic of 920° C. From this ternary eutectic the labeled isotherms diverge outward to form the steep walls of this trough. The region in this paper for which calculations were made is the heavy diagonal line toward the left-hand wall of this trough which marks the boundary between the regions of iron, wustite and liquid.

Figure 5 is a plot after Turkdogan and Kor¹³ of the conditions of oxygen and sulfur potential given as a function of temperature to maintain this four phase equilibrium (three condensed phases plus gas). This plot is not for a system of constant composition but for the composition along the solid line shown in the previous figure. As temperature rises, the oxygen partial pressure is shown to rise, but interestingly, the sulfur partial pressure shown on a log scale drops sharply. Part of this drop can be attributed to a shift in sulfur solubility of the liquid phase to lower sulfur levels as temperature rises; nevertheless, the rapid drop in sulfur

partial pressure is steeper than would be predicted merely by this shift in composition. Even at 1300° C, the chemical potential of sulfur, as measured by the parameter, $-RT\ln P_{S_2}$, is about 45,000 calories per gram mole corresponding to a partial pressure of sulfur of 5.58×10^{-7} atm. This is a fortuitous aspect of the Fe-O-S system; i.e., the thermodynamic calculations for desulfurization show improvement with higher temperatures. Figure 6 is a plot for the Fe-O-S system similar to those for the lime-based systems in which this improved degree of desulfurization with increasing temperature is shown. The increased dosage of iron is also shown. For example at 1300° C, an iron dosage for the coal composition for these calculations would be 15 grams per 100 grams of coal.

One of the objectives of this study is to develop an interactive computer program such that an operator of a slagging combustor can enter coal compositions and combustion conditions and determine the optimum process conditions required. Figure 7 shows the air requirements for 100 grams of dry coal and the theoretical percent sulfur removal which can be achieved.

Figure 8 shows the calculated concentrations of the major gas species as a function of temperature for the equilibrium between Fe/FeO/L/G. The predominant species for these reducing conditions (corresponding to a combustion stoichiometry of approximately 55 % of the required air for complete combustion) are N_2 and CO followed by CO_2 , H_2 , and H_2O in that order. The total sulfur pressure is the sum of all the sulfur-bearing species with H_2S being the predominant sulfur carrier. Lower rank coals with higher hydrogen water vapor contents would be expected to carry more sulfur into the gas phase. Since the pressure of the sulfur species, S_2 , is fixed by the phase equilibrium, the actual amount of sulfur in the gas phase is determined principally by equation (3). The partial pressure of H_2S is seen via the expression for the equilibrium constant K_3 to be a function of the square root of the pressure of S_2 , but varies linearly with the pressure of H_2 . It follows, therefore, that iron oxysulfide would perform best on dry, high-rank coals.

Figure 9 shows the expected levels of SO_2 which would be expected as a function of the moisture content of the coal as expressed in pounds of SO_2 per million BTUs of gross calorific power of the coal burned under stoichiometric conditions. Since moisture adds hydrogen to the combustion gas, the same arguments as expressed above apply, and as a result, the sulfur capture is poorer for more moist coals.

Figure 10 shows the three major sulfur species in the gas phase which occur at 1200°C. for the equilibrium between Fe/FeO/L/G. Under these reducing conditions as shown on the logarithmic scale, hydrogen sulfide predominates over sulfur dioxide. On the abscissa is given the water-vapor content. The partial pressure of hydrogen sulfide on this logarithmic scale is increased with increasing moisture content of the coal as shown.

Figure 11 shows the effect of total pressure on SO_2 concentration. The effect is minimal except for pressures significantly below one atmosphere.

Calculations on Fe/FeO/L/G Equilibria and Mass and Heat Balances on Typical Illinois #6 Coals:

The coal seam which has been studied most extensively in clean-coal programs is Illinois #6. Five representative coals from this seam are characterized with respect to their assays and calorific values in Table 1. This information was then entered into the interactive program to determine the equilibrium sulfur pressures of the predominant gas species which would be present over the phases: Fe/FeO/L. Tables 2 and 3 compare the results of these calculations with respect to moist and dry coals, respectively. These results are summarized in Figure 12 which gives the equilibrium values of SO_2 under conditions of stoichiometric combustion vs. temperature. The moist coal IBC-108 which contains 45 percent moisture (essentially a slurry) shows the highest SO_2 content of the combustion products, as is expected. The lowest sulfur content is for IBC-109 which has a starting composition of only 1.14% sulfur compared with the other coals which range up to 4.52% sulfur for IBC-105.

The developed program also yields mass and heat balances with respect to the gasification stage (first stage of combustion) as well as the second stage (stoichiometric combustion). An example of the heat and mass balance information for the Illinois Coal IBC-102 is shown in Table 4. In Appendix A is shown the method of calculation and the assumptions used in the calculation. Also included in the appendix are outputs from the HSC program¹⁵ for the equilibrium of the coal gas with the condensed phases Fe/FeO/L.

The distribution of thermal energy with respect to the first and second stages of combustion is an important consideration. If too much energy is expended in the first stage, then the burner walls must be indirectly cooled in order to prevent severe erosion especially from the fluxing properties of the iron oxysulfide liquid. If, however, the first stage is nearly autogenous, then there may be difficulties in maintaining the flame front unless a degree of preheat is applied. The calculations show the first stage is not only autogenous at 1200° C, but that approximately 1 to 2 percent of the thermal energy of the as-received coal is present in excess to maintain the flame. Pre-drying of the coal would, of course, increase the excess heat available. In order to burn these typical coals at temperatures significantly above 1200° C, preheat of the combustion air and/or pre-drying of the coal is necessary; also, drying of the coal is desirable from the viewpoint of reduction of sulfur levels.

CONCLUSIONS

The following can be concluded from this analysis:

- * Lime added to combustion gases under oxidizing conditions to form sulfate as a reaction product is not practical as a sulfur sorbent at temperatures above 1175° C.
- * Lime added under reducing conditions to form the compound CaS, is effective up to temperatures well above 2000° C.
- * In the Fe-O-S system for the four-phase contact, Fe/FeO/L/G, higher temperatures result in greater degrees of desulfurization for the range of temperatures studied.
- * The role of moisture and hydrogen in the coal has an adverse effect on the degree of desulfurization.
- * For typical Illinois No 6 coals which were studied, at 1200° C and under conditions where the equilibrium Fe/FeO/L/G is maintained, heat balance calculations indicate that combustion is nearly autogenous. To sustain combustion at higher temperatures, heat exchange between the combustion products and inlet air would be required.
- * Inference is made that for iron oxysulfide as a sorbent, this liquid phase should exhibit a higher degree of utilization in liquid droplets than solid lime sorbents. Furthermore the kinetics of liquid/gas interactions should be more favorable than solid/gas interactions. This hypothesis will require further study in a dynamic burner system.

REFERENCES

1. Hepworth, M. T. and Reid, K. J.: Slagging Combustor Review, Final Report MRRC, University of Minnesota December, 1988
2. Private Communication: R. Diehl Avco Research Laboratories, Everett, Mass.
3. Hepworth, M. T. and Wicker G. R.: "Iron Oxide as a Desulfurizing Agent in a Slagging Coal Combustor", Pyrometallurgy "87, Institution of Mining and Metallurgy, London, 1987. and Hepworth, M. T., U. S. Patents 4,572,085 (2/25/86), 4,598,652 (7/8/86), and 4,599,955 (7/15/86).
4. Lachapelle, David G.: "EPA's LIMB Technology Development Program," Chemical Engineering Progress, May 1985, pps. 56-62.
5. Rao, Y. K.: Stoichiometry and Thermodynamics of Metallurgical Processes, Cambridge University Press, Cambridge, 1985.

6. Hepworth, M. T.: Molten Iron Oxysulfide as a Superior Sulfur Sorbent DOE/DE-FG22-89PC89778 Third Quarterly Report March 1 - May 31, 1990.
7. Harvey, Richard D.: Illinois Geological Survey, Letter of 9/8/89 to M.T. Hepworth.
8. Kubaschewski, O. and Alcock, C. B.: Metallurgical Thermochemistry, Pergamon Press, 1979.
9. Darken, L. S. and Gurry, R. W., J. Am. Chem. Soc., 1945, Vol 67. pps. 1398-1412; 1946, vol 68, pps. 798-816.
10. Bog, S. and Rosenqvist, T.: The Physical Chemistry of Metallic Solutions and Intermetallic Compounds, Paper 6B, NPL Symposium No 9, Vol II, 1959.
11. Rosenqvist, T. and Hartvig, T.: Roy. Norweg. Concil Sci. and Ind. Res., Rep. No 12, Part II, 1958.
12. Burgmann, W., Urbain, G., and Froberg, M. G.: IRSID Saint Germain-en-Laye, France, January 1968.
13. Turkdogan, E. T. and Kor, G. J. W.: "Sulfides and Oxides in Fe-Mn Alloys: Part I, Phase Relations in the Fe-Mn-S-O System", Metallurgical Transactions, Vol 2, June 1971, pps. 1561-1578.
14. Hilty, D. C. and Crafts, W: Trans. AIME, 194, 1952, p.1307.
15. HSC - Software Version 3.31, Outokumpu Research Center, Pori, Finland.

DOERPT4

TABLE 1. COAL COMPOSITIONS

Analyses of Samples from the IBC Lots					
Illinois #6 Coal (Moisture Free Value)					
Lot	IBC-104	IBC-105	IBC-107	IBC-108	IBC-109
Moisture %	10.5	9.4	9.3	45.0	9.2
V Matter %	28.3	36.7	40.0	41.3	34.9
Fixed C %	3.3	44.8	48.5	54.9	56.8
H-T Ash %	38.4	18.5	11.5	3.8	8.3
Carbon %	46.78	63.6	68.11	76.2	74.95
Hydrogen %	3.41	4.58	5.0	5.41	4.95
Nitrogen %	0.88	1.19	1.2	1.56	1.76
Oxygen %	8.25	7.55	10.56	10.39	8.93
Sulfur %	4.17	4.52	3.87	2.63	1.14
BTU/lb	8522	11540	12224	13700	13301

TABLE 2. CALCULATED CONDITIONS¹ OF COMBUSTION FOR MOIST COALS IN EQUILIBRIUM WITH Fe/FeO/LIQUID

Results of Calculations					
Pressure Atmospheres	IBC-104	IBC-105	IBC-107	IBC-108	IEC-109
P _{CO}	0.2051	0.1967	0.1977	0.1972	0.1967
P _{CO2}	0.0643	0.0617	0.0620	0.0618	0.0617
P _{H2}	0.0830	0.0764	0.0769	0.1186	0.0688
P _{H2O}	0.0648	0.0596	0.0600	0.0925	0.0537
P _{N2}	0.5826	0.6053	0.6030	0.5294	0.6188
P _{O2}	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²
P _{H2S}	2.95x10 ⁻⁴	2.72x10 ⁻⁴	2.74x10 ⁻⁴	4.22x10 ⁻⁴	2.44x10 ⁻⁴
P _{SO2}	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶
P _{COS}	2.51x10 ⁻⁵	3.37x10 ⁻⁵	3.39x10 ⁻⁵	3.38x10 ⁻⁵	3.37x10 ⁻⁵
P _{SO}	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷
P _{S2}	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷
P _{SO3}	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴
Air, M ³ STP/100kg	238.13	350.75	372.34	366.38	422.29
S Removal %	96.30	95.52	94.39	86.31	80.88
SO ₂ LB/MMBTU	0.362	0.351	0.355	0.525	0.327
Dosage Fe ₃ O ₄ kg/100kg	24.35	26.18	22.15	13.77	5.59

1 Calculated conditions at 1200° C.

TABLE 3. CALCULATED CONDITIONS¹ OF COMBUSTION FOR MOISTURE-FREE COAL IN EQUILIBRIUM WITH Fe/FeO/LIQUID

Results of Calculations					
Pressure Atmospheres	IBC-104	IBC-105	IBC-107	IBC-108	IBC-109
P _{CO}	0.2046	0.1964	0.1975	0.1961	0.1965
P _{CO2}	0.0642	0.0616	0.0619	0.0615	0.0616
P _{H2}	0.0603	0.0621	0.0636	0.0611	0.0569
P _{H2O}	0.0470	0.0484	0.0496	0.0477	0.0444
N ₂	0.6237	0.6312	0.6271	0.6334	0.6404
P _{O2}	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²	1.1x10 ⁻¹²
P _{H2S}	2.14x10 ⁻⁴	2.21x10 ⁻⁴	2.26x10 ⁻⁴	2.17x10 ⁻⁴	2.03x10 ⁻⁴
P _{SO2}	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶	1.07x10 ⁻⁶
P _{COS}	2.51x10 ⁻⁵	3.37x10 ⁻⁵	3.39x10 ⁻⁵	3.36x10 ⁻⁵	3.37x10 ⁻⁵
P _{SO}	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷	3.44x10 ⁻⁷
P _{S2}	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷	7.23x10 ⁻⁷
P _{SO3}	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴	5.4x10 ⁻¹⁴
Air, M ³ STP/100kg	255.533	366.33	387.74	440.94	437.53
S Removal %	97.19	96.25	95.24	92.38	83.75
SO ₂ LB/MMBTU	0.274	0.293	0.301	0.292	0.278
Dosage Fe ₃ O ₄ kg/100kg	24.58	26.38	22.35	14.73	5.79

1 Calculated conditions at 1200° C.

**Predominance Diagram
Ca-S-O System
Solid Line - 1000° C
Dashed Line - 1300° C**

FIGURE 1.

CaO/CaS/Gas System
SO₂ Concentration & Lime Dosage g/100g
Dry Coal vs. Temperature O₂ Pressure
10⁻¹² atm.

FIGURE 2.

CaO/CaSO₄/Gas System
SO₂ Concentration & Lime Dosage g/100g
Dry Coal vs. Temperature O₂ Pressure:
0.05 Atmospheres.

FIGURE 3.

**Ternary Section Fe/S/O System.
After: Bog and Rosenqvist & Hilty
and Crafts.**

FIGURE 4.

**Fe/FeO/Liquid/Gas System
Chemical Potential O, S.**

FIGURE 5.

Fe/FeO/Liquid/Gas System
SO₂ Concentration and Iron Dosage
g/100 Dry Coal vs. Temperature

FIGURE 6.

**Fe/FeO/Liquid/Gas System
Sulfur Removal and Air Dosage
vs. Temperature**

FIGURE 7.

Fe/FeO/Liquid System
Partial Pressure (atm) vs. Temperature

FIGURE 8.

**Fe/FeO/Liquid/Gas System
SO₂ Concentration vs. Moisture
g/100g Dry Coal at 1200° C**

FIGURE 9.

**Fe/FeO/Liquid/Gas System
Partial Pressure vs. Moisture
g/100g Dry Coal at 1200° C**

FIGURE 10.

Fe/FeO/Liquid/Gas System
Effect of Pressure upon Desulfurization

FIGURE 11.

Comparative Effect of Temperature upon Desulfurization

FIGURE 12.

APPENDIX A

Mass and Heat Balance for Coal IBC-102

TABLE 4. MASS AND HEAT BALANCE, COAL IBC-102

INPUT			OUTPUT		
Substance	Moisture	Dry	Substance	Moisture	Dry
<u>Coal</u>			<u>Coal gas</u>		
C	73.92	73.92	CO	131.23	131.23
H	5.29	5.29	CO ₂	64.64	64.64
N	1.52	1.52	H ₂	3.86	2.97
O	9.02	9.02	H ₂ O	26.89	20.68
S	3.29	3.29	N ₂	402.64	425.87
H ₂ O	14.2		O ₂	8x10 ⁻¹⁰	8x10 ⁻¹⁰
Al ₂ O ₃	1.333	1.333	H ₂ S	0.232	0.178
CaO	0.267	0.267	COS	0.048	0.048
Fe ₂ O ₃	1.51	1.51	SO ₂	0.00165	0.00165
SiO ₂	3.298	3.298	S ₂	0.00111	0.00111
Other	0.492	0.492	SO	0.0004	0.0004
<u>Primary Air</u>			SO ₃	1x10 ⁻¹⁰	1x10 ⁻¹⁰
O ₂	121.8	128.85	<u>Oxysulfide</u>		
N ₂	400.92	424.14	Fe	13.354	13.575
Fe ₂ O ₄	17	17.31	O	2.669	2.713
			S	3.043	3.093
			<u>Slag</u>		
			CaO*SiO ₂	0.553	0.553
			Al ₂ O ₃ *SiO ₂	2.119	2.119
			SiO ₂	2.226	2.226
			Other	0.492	0.492
<u>Total</u>	653.92	670.3	<u>Total</u>	653.99	670.39
ΔH (MJ)	-3157.8	-3157.8	ΔH ₂ (MJ)	-2820.0	-2711.9
ΔH ₁ (MJ)	-337.7	-445.8			

Mass and Heat Balance for IBC-102

1. Composition of Coal: (Illinois #2)

Recent analysis of Illinois #2 sample: (Moisture Free Value)

Moisture: 14.2, Volatile Matter: 39.8

Fixed Carbon: 53.3 H-T Ash: 6.9

Carbon: 73.92 Hydrogen: 5.29 Nitrogen: 1.52

Oxygen: 9.02 Sulfur: 3.29

Gross Calorific Value: 13582 Btu/lb

Major Elements in Ash: (%) (Average IL Coal)

Al₂O₃: 19.31 CaO: 3.87 Fe₂O₃: 21.88

SiO₂: 47.79 Other: 7.15

2. Calculation

Calculation based on 100 kg dry coal.

Using the interactive program, the following results are obtained.

[1] Fe/FeO/Liquid System

(1) 114.2 kg received coal

Condition: 1200°C

Composition of Fe-S-O matte: S 15.96%, O 14.00%, Fe 70.04%

The amount of Primary Air under STP: 406.27 m³

The Percent of Sulfur Removal: 92.52%

The SO₂ Emission Concentration (lb/mm Btu): 0.36

The Dosage of Fe₃O₄: 17.00 kg

The Composition of Clean Fuel Gas: (P_r=1 atm)

P _{CO} : 0.196	P _{CO2} : 6.14x10 ⁻²	P _{N2} : 0.600
P _{H2} : 7.99x10 ⁻²	P _{H2O} : 6.24x10 ⁻²	P _{O2} : 1.08x10 ⁻¹²
P _{H2S} : 2.84x10 ⁻⁴	P _{COs} : 3.35x10 ⁻⁵	P _{SO2} : 1.07x10 ⁻⁶
P _{S2} : 7.23x10 ⁻⁷	P _{SO} : 3.44x10 ⁻⁷	P _{SO3} : 5.40x10 ⁻¹⁴

[a] Mass Balance

I) INPUT: 25°C, 653.92 kg

Coal: 100 kg dry coal + 14.2 kg moisture = 114.2 kg

H₂O: 14.2 kg C: 73.92 kg H: 5.29 kg

N: 1.52 kg O: 9.02 kg S: 3.29 kg

Major Elements in Ash:

Al₂O₃: 1.333 kg CaO: 0.267 kg Fe₂O₃: 1.510 kg

SiO₂: 3.298 kg Other: 0.492 kg

Primary Air: Air Amount Under STP: 406.27 m³

O₂: 121.80 kg N₂: 400.92 kg

Dosage of Fe₃O₄: 17.00 kg

II) OUTPUT: 1200°C, 653.99 kg

Clean Fuel Gas:

CO: 131.23 kg CO₂: 64.64 kg COS: 0.048 kg

N₂: 402.64 kg H₂S: 0.232 kg SO₂: 1.65x10⁻³ kg

S₂: 1.11x10⁻³ kg SO: 3.96x10⁻⁴ kg SO₃: 1.04x10⁻¹⁰ kg

H₂: 3.86 kg H₂O: 26.89 kg O₂: 8.27x10⁻¹⁰ kg

Slag:

a) Fe-S-O Matte: Fe: 13.354 kg O: 2.669 kg S: 3.043 kg

b) CaO*SiO₂: 0.553 kg Al₂O₃*SiO₂: 2.119 kg

SiO₂: 2.226 kg other: 0.492 kg

[b] Heat Balance

I) The Method of Calculation

The calorific value of coal is the amount of heat released when a unit quantity of the fuel is burned in oxygen to completion and the products of combustion are cooled back to the reference state (25°C) at which the calorific value determination is being made.

From the scheme of heat balance calculation, the heat balance of gasification can be calculated by the following equation:

$$\Delta H_1 = \Delta H - \Delta H_2$$

ΔH : the calorific value of coal: For the coal Illinois #2,

$$\Delta H = 13582 \text{ Btu/lb}$$

ΔH_2 : the heat from the complete combustion of clean fuel gas and slag at 1120°C to the same product state under which the calorific value is measured.

We use the method because the coal composition are very complex and the calorific value of coal and the composition of clean fuel gas and slag have been known. The calculation of H_2 can be made easily by the HSC-SOFTWARE program.

II) The Result of Calculation

$$\begin{aligned} \Delta H &= -13582(\text{Btu/lb}) \times 1.0544 \times 10^3 (\text{J/Btu}) \times 100 (\text{kg}) \times 2.205 (\text{lb/kg}) \times 10^6 \\ &= -3157.75 \text{ MJ} \end{aligned}$$

$$\Delta H_2 = -2820.04 \text{ MJ}$$

So the heat of gasification process:

$$\Delta H_1 = -337.71 \text{ MJ}$$

(2) 100 kg dry coal

Condition: 1200°C

Composition of Fe-S-O matte: S 15.96%, O 14.00%, Fe 70.04%

The amount of Primary Air under STP: 429.80 m³

The Percent of Sulfur Removal: 94.05%

The SO₂ Emission Concentration (lb/mm Btu): 0.29

The Dosage of Fe₃O₄: 17.31 kg

The Composition of Clean Fuel Gas: ($P_T=1 \text{ atm}$)

P_{CO} : 0.195	P_{CO_2} : 6.13×10^{-2}	P_{N_2} : 0.634
P_{H_2} : 6.13×10^{-2}	P_{H_2O} : 4.79×10^{-2}	P_{O_2} : 1.08×10^{-12}
P_{H_2S} : 2.18×10^{-4}	P_{COS} : 3.35×10^{-5}	P_{SO_2} : 1.07×10^{-6}
P_{S_2} : 7.23×10^{-7}	P_{SO} : 3.44×10^{-7}	P_{SO_3} : 5.40×10^{-14}

[a] Mass Balance

I) INPUT: 25°C, 670.30 kg

Coal: 100 kg dry coal

C: 73.92 kg H: 5.29 kg N: 1.52 kg

O: 9.02 kg S: 3.29 kg

Major Elements in Ash:

Al₂O₃: 1.333 kg CaO: 0.267 kg Fe₂O₃: 1.510 kg

SiO₂: 3.298 kg Other: 0.492 kg

Primary Air: Air Amount Under STP: 429.80 m³

O₂: 128.85 kg N₂: 424.14 kg

Dosage of Fe₃O₄: 17.31 kg

II) OUTPUT: 1200°C, 670.39 kg

Clean Fuel Gas:

CO: 131.23 kg CO₂: 64.64 kg COS: 0.048 kg

N₂: 425.87 kg H₂S: 0.178 kg SO₂: 1.65x10⁻³ kg

S₂: 1.11x10⁻³ kg SO: 3.97x10⁻⁴ kg SO₃: 1.04x10⁻¹⁰ kg

H₂: 2.97 kg H₂O: 20.68 kg O₂: 8.29x10⁻¹⁰ kg

Slag:

a) Fe-S-O Matte: Fe: 13.575 kg O: 2.713 kg S: 3.093 kg

b) CaO*SiO₂: 0.553 kg Al₂O₃*SiO₂: 2.119 kg

SiO₂: 2.226 kg other: 0.492 kg

[b] Heat Balance

The Result of Calculation

$$\begin{aligned}\Delta H &= -13582(\text{Btu/lb}) \times 1.0544 \times 10^3 (\text{J/Btu}) \times 100(\text{kg}) \times 2.205(\text{lb/kg}) \times 10^6 \\ &= -3157.75 \text{ MJ}\end{aligned}$$

$$\Delta H_2 = -2711.94 \text{ MJ}$$

So the heat of gasification process:

$$\Delta H_1 = -445.81 \text{ MJ}$$

[2] Liquid System

(1) 114.2 kg received coal

According to the data from Shima & Naldrett, the following data are selected for calculation.

Condition: 1200°C

Composition of Fe-S-O matte: S 27.68%, O 1.829%, Fe 70.491%

The amount of Primary Air under STP: 311.88 m³

The Percent of Sulfur Removal: 78.25%

The SO₂ Emission Concentration (lb/mm Btu): 1.0

The Dosage of Fe₃O₄: 7.60 kg

The Composition of Clean Fuel Gas: (P_T=1 atm)

P _{CO} : 0.272	P _{CO2} : 2.60x10 ⁻²	P _{N2} : 0.536
P _{H2} : 0.133	P _{H2O} : 3.16x10 ⁻²	P _{O2} : 1.00x10 ⁻¹³
P _{H2S} : 9.80x10 ⁻⁴	P _{COs} : 9.67x10 ⁻⁵	P _{SO2} : 2.06x10 ⁻⁷
P _{S2} : 3.10x10 ⁻⁶	P _{SO} : 2.17x10 ⁻⁷	P _{SO3} : 3.15x10 ⁻¹⁵

[a] Mass Balance

I) INPUT: 25°C, 523.08 kg

Coal: 100 kg dry coal + 14.2 kg moisture = 114.2 kg

H₂O: 14.2 kg C: 73.92 kg H: 5.29 kg

N: 1.52 kg O: 9.02 kg S: 3.29 kg

Major Elements in Ash:

Al₂O₃: 1.333 kg CaO: 0.267 kg Fe₂O₃: 1.510 kg

SiO₂: 3.298 kg Other: 0.492 kg

Primary Air: Air Amount Under STP: 311.88 m³

O₂: 93.50 kg N₂: 307.78 kg

Dosage of Fe₃O₄: 7.60 kg

II) OUTPUT: 1200°C, 523.11 kg

Clean Fuel Gas:

CO: 157.33 kg	CO ₂ : 23.58 kg	COS: 0.120 kg
N ₂ : 309.44 kg	H ₂ S: 0.688 kg	SO ₂ : 2.72x10 ⁻⁴ kg
S ₂ : 4.10x10 ⁻³ kg	SO: 2.15x10 ⁻⁴ kg	SO ₃ : 5.20x10 ⁻¹² kg
H ₂ : 5.53 kg	H ₂ O: 11.73 kg	O ₂ : 6.60x10 ⁻¹¹ kg

Slag:

a) Fe-S-O Matte: Fe: 6.554 kg O: 0.170 kg S: 2.574 kg
 b) CaO*SiO₂: 0.553 kg Al₂O₃*SiO₂: 2.119 kg
 SiO₂: 2.226 kg other: 0.492 kg

[b] Heat Balance

The Result of Calculation

$$\Delta H = -13582 (\text{Btu/lb}) \times 1.0544 \times 10^3 (\text{J/Btu}) \times 100 (\text{kg}) \times 2.205 (\text{lb/kg}) \times 10^6$$

$$= -3157.75 \text{ MJ}$$

$$\Delta H_2 = -3120.02 \text{ MJ}$$

So the heat of gasification process:

$$\Delta H_1 = -37.73 \text{ MJ}$$

(2) 100 kg dry coal

Condition: 1200°C

Composition of Fe-S-O matte: S 27.68%, O 1.829%, Fe 70.491%

The amount of Primary Air under STP: 345.47 m³

The Percent of Sulfur Removal: 82.79%

The SO₂ Emission Concentration (lb/mm Btu): 0.83

The Dosage of Fe₃O₄: 8.13 kg

The Composition of Clean Fuel Gas: (P_T=1 atm)

P _{CO} : 0.267	P _{CO2} : 2.55x10 ⁻²	P _{N2} : 0.582
P _{H2} : 0.100	P _{H2O} : 2.38x10 ⁻²	P _{O2} : 1.00x10 ⁻¹³
P _{H2S} : 7.39x10 ⁻⁴	P _{COS} : 9.49x10 ⁻⁵	P _{SO2} : 2.06x10 ⁻⁷
P _{S2} : 3.10x10 ⁻⁶	P _{SO} : 2.17x10 ⁻⁷	P _{SO3} : 3.15x10 ⁻¹⁵

[a] Mass Balance

I) INPUT: 25°C, 552.62 kg

Coal: 100 kg dry coal

C: 73.92 kg H: 5.29 kg N: 1.52 kg
O: 9.02 kg S: 3.29 kg

Major Elements in Ash:

Al₂O₃: 1.333 kg CaO: 0.267 kg Fe₂O₃: 1.510 kg
SiO₂: 3.298 kg Other: 0.492 kg

Primary Air: Air Amount Under STP: 345.47 m³

O₂: 103.57 kg N₂: 340.92 kg

Dosage of Fe₃O₄: 8.13 kg

II) OUTPUT: 1200°C, 552.66 kg

Clean Fuel Gas:

CO: 157.33 kg CO₂: 23.58 kg COS: 0.120 kg
N₂: 342.60 kg H₂S: 0.529 kg SO₂: 2.77x10⁻⁴ kg
S₂: 4.18x10⁻³ kg SO: 2.19x10⁻⁴ kg SO₃: 5.30x10⁻¹² kg
H₂: 4.25 kg H₂O: 9.02 kg O₂: 6.72x10⁻¹¹ kg

Slag:

a) Fe-S-O Matte: Fe: 6.935 kg O: 0.180 kg S: 2.723 kg
b) CaO*SiO₂: 0.553 kg Al₂O₃*SiO₂: 2.119 kg
 SiO₂: 2.226 kg other: 0.492 kg

[b] Heat Balance

The Result of Calculation

$$\Delta H = -13582 (\text{Btu/lb}) \times 1.0544 \times 10^3 (\text{J/Btu}) \times 100 (\text{kg}) \times 2.205 (\text{lb/kg}) \times 10^6 \\ = -3157.75 \text{ MJ}$$

$$\Delta H_2 = -2982.89 \text{ MJ}$$

So the heat of gasification process:

$$\Delta H_1 = -174.86 \text{ MJ}$$

The gasification process is exothermic. Considering the heat losses in process, the process is autothermic.

PRIMARY PROCESS OF COAL CONVERSION

HEAT BALANCE CALCULATION SCHEME

Fe/FeO/L

Moist Coal

***** MASS BALANCE I ***** MASS BALANCE II *****

	INPUT kmol	OUTPUT kmol	DIFF. kmol	INPUT kg	OUTPUT kg	DIFF. kg
Al	0.03	0.03	0.00	0.71	0.71	0.00
C	6.16	6.16	0.00	73.93	73.97	0.04
Ca	0.00	0.00	0.00	0.19	0.19	0.00
Fe	0.24	0.24	-0.00	13.36	13.36	-0.00
H	6.82	6.82	-0.00	6.88	6.88	-0.00
N	28.75	28.75	0.00	402.66	402.66	0.00
O	16.41	16.41	0.00	262.50	262.55	0.04
S	0.10	0.10	0.00	3.29	3.29	0.00
Si	0.05	0.05	-0.00	1.54	1.54	-0.00

***** HEAT BALANCE *****

INPUT:

=====

COMPONENT	TEMPERATURE C	AMOUNT kmol	kg Nm3	HEAT CONTENT MJ
CO(g)	1200.00	4.69	105.02	-342.12
CO2(g)	1200.00	1.47	32.92	-491.32
COS(g)	1200.00	0.00	0.02	-0.07
N2(g)	1200.00	14.37	322.17	534.46
H2S(g)	1200.00	0.01	0.15	0.20
H2(g)	1200.00	1.91	42.87	68.06
H2O(g)	1200.00	1.49	33.46	-291.60
O2(g)	25.00	3.48	78.11	0.00
CaO*SiO2	1200.00	0.00	0.55	-7.05
Al2O3*SiO2	1200.00	0.01	2.12	-31.08
FeO*SiO2	1200.00	0.00	0.00	0.00
SiO2	1200.00	0.04	2.23	-30.80
FeS	1200.00	0.07	6.37	0.65
FeO	1200.00	0.17	11.98	-34.06
S	1200.00	0.02	0.72	1.14
EXTRA INPUT HEAT OF THE PROCESS				0.00

OUTPUT:

=====

COMPONENT	TEMPERATURE C	AMOUNT kmol	kg Nm3	HEAT CONTENT MJ
CO2(g)	25.00	6.16	138.04	-2423.50
N2(g)	25.00	14.37	322.17	0.00
H2O(g)	25.00	3.41	76.45	-824.80
SO2(g)	25.00	0.10	2.30	-30.46
Fe3O4	25.00	0.07	17.00	-82.11
CaO	25.00	0.00	0.27	-3.05
Al2O3	25.00	0.01	1.34	-22.02
SiO2	25.00	0.05	3.30	-49.89
Fe2O3	25.00	0.01	1.51	-7.81
HEAT LOSSES				0.00

HEAT IS RELEASED / MJ

-2820.04

Fe/FeO/L
DRY COAL

***** MASS BALANCE I ***** MASS BALANCE II *****

	INPUT kmol	OUTPUT kmol	DIFF. kmol	INPUT kg	OUTPUT kg	DIFF. kg
Al	0.03	0.03	0.00	0.71	0.71	0.00
C	6.16	6.16	0.00	73.93	73.94	0.01
Ca	0.00	0.00	0.00	0.19	0.19	0.00
Fe	0.24	0.24	0.00	13.58	13.58	0.00
H	5.25	5.25	-0.00	5.29	5.29	-0.00
N	30.41	30.41	0.00	425.90	425.90	0.00
O	15.62	15.62	-0.00	249.95	249.95	-0.00
S	0.10	0.10	0.00	3.30	3.30	0.00
Si	0.05	0.05	-0.00	1.54	1.54	-0.00

***** HEAT BALANCE *****

INPUT:

=====

COMPONENT	TEMPERATURE C	AMOUNT kmol	kg Nm3	HEAT CONTENT MJ
CO(g)	1200.00	4.69	105.02	-342.12
CO2(g)	1200.00	1.47	32.92	-491.32
COS(g)	1200.00	0.00	0.02	-0.07
N2(g)	1200.00	15.20	340.76	565.30
H2S(g)	1200.00	0.01	0.12	0.16
H2(g)	1200.00	1.47	32.97	52.34
H2O(g)	1200.00	1.15	25.73	-224.23
O2(g)	25.00	3.26	73.15	0.00
CaO*SiO2	1200.00	0.00	0.55	-7.05
Al2O3*SiO2	1200.00	0.01	2.12	-31.08
FeO*SiO2	1200.00	0.00	0.00	0.00
SiO2	1200.00	0.04	2.23	-30.80
FeS	1200.00	0.07	6.47	0.66
FeO	1200.00	0.17	12.18	-34.63
S	1200.00	0.02	0.74	1.17
EXTRA INPUT HEAT OF THE PROCESS				0.00

OUTPUT:

=====

COMPONENT	TEMPERATURE C	AMOUNT kmol	kg Nm3	HEAT CONTENT MJ
CO2(g)	25.00	6.16	137.97	-2422.28
N2(g)	25.00	15.20	340.76	0.00
H2O(g)	25.00	2.62	58.80	-634.38
SO2(g)	25.00	0.10	2.31	-30.59
Fe3O4	25.00	0.07	17.31	-83.61
CaO	25.00	0.00	0.27	-3.05
Al2O3	25.00	0.01	1.34	-22.02
SiO2	25.00	0.05	3.30	-49.89
Fe2O3	25.00	0.01	1.51	-7.81
HEAT LOSSES				0.00

HEAT IS RELEASED / MJ

-2711.94

END

**DATE
FILMED
9/22/92**