RECEIVED
NOV 10 1998
OSTI

Investigation of Combined SO_2/NO_x Removal By Ceria Sorbents

**Final Report
December 1992 - August 1996**

**By
Ates Akyurtlu
Jale F. Akyurtlu**

Work Performed Under Contract No.: DE-PS22-92MT92018

For
U.S. Department of Energy
Office of Fossil Energy
Federal Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880

By
Hampton University
Department of Chemical Engineering
Hampton, Virginia 23668

Disclaimer

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owed rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

SUMMARY

This final report describes the work done under the sponsorship of the U.S. DOE for the support of advanced fossil resource utilization research at historically black colleges and universities, Grant No. DE-PS22-92MT920 on "Investigation of Combined SO_2/NO_x Removal by Ceria Sorbents". The work was conducted at the Department of Chemical Engineering of Hampton University. The industrial partner was Malcolm Pirnie, Inc. Environmental Engineers, Scientists and Planners, who handled the metal analysis and XRD measurements on the solid sorbents; they have also supplied the flyash used in the experimental program. The development of a commercial process concept, economic analysis, and evaluation of process alternatives were undertaken by TECOGEN of Waltham, MA.

The objectives of this research were:

1. To obtain a rate expression for the sulfation and regeneration of alumina supported CeO_2 sorbents,
2. To determine the effects of ammonia on the sulfation of the sorbent,
3. To determine the effects of fly ash on the sulfation and regeneration of the sorbent,
4. To model the sulfation and regeneration reactors for a commercial scale combined SO_2/NO_x removal facility based on $\text{CeO}_2/\text{Al}_2\text{O}_3$ sorbent.

5. To compare the economics of the process to that of the copper oxide process.

For the sulfation reaction an activation energy of 19 kJ/mole was obtained. The dependence of sulfation rate on SO_2 partial pressure changed from 0,83 at 773 K to 1.33 at 873 K.

For regeneration with hydrogen, the activation energy was found to be 114 kJ/mol (27 kcal/mol). The activation energy for regeneration with methane is higher, 130 kJ/mol. The dependence of regeneration rate on hydrogen and SO_2 partial pressures was explained through the use of Langmuir-Hinshelwood kinetics.

No definite conclusions could be drawn on the effect of ammonia on sulfation from the TGA data alone due to the complexity of the reactions taking place.

The initial rate of sulfation appears to be slightly improved by the presence of flyash. No significant effect of ammonia was observed in the presence of flyash.

The modeling and evaluation of the commercial scale ceria process was done by TECOGEN of Waltham, MA. Their results indicate that the copper oxide process has a lower overall cost of SO_2 removal mainly because the operating temperature allows the use of carbon steel equipment while the ceria process operates where stainless steel have to be used.

TABLE OF CONTENTS

	<u>Page</u>
I. Introduction	1
I.A. Background Information	
I.A.1. Copper Oxide-Based Sorbents	
I.A.2. Ceria-Based Sorbents	
I.A.3. Modeling of Moving Bed Reactors	
II. Description of the Project	
II.A. Project Objectives	
II.B. Project Tasks	
III. Sorbent Preparation and Characterization	
IV. Standard Sulfation-Regeneration Runs with Pellets	
IV.A. Sulfation Experiments	
IV.B. Regeneration Experiments	
V. Results of Runs with Sorbent Pellets	
V.A. Experiments with Standard TGA Configuration	
V.B. Experiments with Downflow of TGA Gas	
V.C. Effect of Cycling	
V.D. Effect of Mass Transfer Limitations	
V.E. Effect of Temperature	
V.F. Effect of Water Vapor	
V.G. Effect of Ammonia	
VI. Experiments with Sorbent Particles	
VI.A. Regeneration of Sulfated Sorbent	
VI.A.1. Regeneration with Hydrogen	

- VI.A.1.a. Data Evaluation
- VI.A.1.b. Results and Discussion
- VI.A.2. Regeneration with Methane
  - VI.A.2.a. Data Evaluation
  - VI.A.2.b. Coking During Regeneration with Methane
  - VI.A.2.c. Effect of Regeneration Gas Composition
  - VI.A.2.d. Effect of Temperature
  - VI.A.2.e. Effects of SO₂ and CO₂
  - VI.A.2.f. Effect of Heating Atmosphere
  - VI.A.2.g. Cycling Behavior with Methane Regeneration
- VI.B. Sulfation of the Sorbent
  - VI.B.1. Effect of Temperature and SO₂ Partial Pressure
  - VI.B.2. Effect of Ammonia on Sulfation
    - VI.B.2.a. Effect of Ammonia in the Presence of Water
  - VI.B.3. Effect of Cerium Content on the Sorbent Performance
    - VI.B.3.a. Effect of Cerium Content on the Order of Sulfation Reaction with Respect to the Solid Reactant
  - VI.B.4. Effect of Flyash on Sulfation
- VII. Evaluation of the Commercial-Scale Ceria Process
- VIII. References
- APPENDIX A. Task Order to TECOGEN
- APPENDIX B. TECOGEN Report

I. INTRODUCTION

Air pollution arising from the emission of sulfur and nitrogen oxides as a result of combustion taking place in boilers, furnaces and engines, has increasingly been recognized as a problem. Acid rain is not the only concern. Nitrogen oxides are involved in photochemical reactions that lead to oxidants such as ozone that are highly toxic to plants and trees. This effect of air pollution is not yet significant, but the damage to forests in Germany has reached alarming proportions. One third of man-made NO_x comes from the power generation industry and manufacturing industries contribute an additional 20%. German standards for NO_x emissions from coal-fired power plants are about four times more stringent than the New Source Performance Standards in the United States. The current federal NO_x emission limits for combustion sources such as process heaters, industrial and utility boilers, and combustion turbines can be readily achieved by most of the NO_x formation control techniques in general use. Since a significant lowering of these limits is anticipated in the near future, new methods to remove SO_2 and NO_x emissions significantly and economically must be developed.

Several approaches may be taken to reduce the SO_2 and NO_x emissions from power generation plants, such as using low sulfur fuel, removing sulfur prior to or during combustion, lowering the

combustion temperature to reduce NO_x formation, increasing the efficiency of the power generation systems, and removing the pollutants after combustion (stack gas cleanup).

There are a number of stack gas desulfurization processes being used commercially. They usually require 5% to 10% of the generated power for operation. The more common of these are: (1) wet scrubbing using lime, limestone, soluble alkali, or dual alkali; and (2) dry absorption with sodium, lime, or limestone. The efficiency and cost of the wet scrubbing systems are usually higher than those of the dry absorber systems. Dry absorption is the least expensive of the stack gas desulfurization processes and can have over 90% SO_2 removal efficiency. Unfortunately these SO_2 scrubbers are not effective in capturing NO_x . Some additives to the scrubbing solution such as chelating agents or phosphorous have been proposed to enhance NO_x removal.

There are several methods for sulfur removal from stack gases at relatively higher temperatures (300°C to 600°C) using regenerable solid sorbents (supported oxides of copper, manganese or cerium). Selective Catalytic Reduction (SCR) is an important process for controlling power plant NO_x emissions. It was commercialized first in Japan in early 1970's and then in Germany. Currently there are over 200 SCR installations in Japan. In United States a few SCR systems have been installed primarily in California. This process removes NO_x in flue gas by catalytically reacting oxides of nitrogen with ammonia to form

nitrogen and water. The catalyst used is either an alumina supported noble metal (such as Pt) on metal monolith or a mixed oxide (such as $V_2O_5/TiO_2/SiO_2$) on ceramic monolith. A major constraint imposed on the heat transfer equipment by a SCR installation is the narrow operating range of the SCR catalysts. Minimum acceptable temperatures usually range between 200°C to 350°C and the maximum operating temperatures are around 400°C to 425°C. One of the factors that influence the operating temperature range of catalysts, particularly vanadium/titanium based ones, is the sulfur content of the flue gas. The SCR catalyst may oxidize up to 5% of SO_2 to SO_3 in addition to about 3% to 5% formed during combustion. This SO_3 , besides poisoning the catalyst, may combine with the unreacted ammonia to form ammonium bisulfate which precipitates at lower temperatures (this temperature is a function of ammonia and SO_3 content of the flue gas) and cause fouling of heat transfer surfaces. Removal of flue gas sulfur prior to ammonia injection will decrease the costs due to reduced catalyst and heat exchanger performance, costly equipment design, and down time for maintenance and cleaning. Since about half the cost of SCR process is catalyst-related, maintaining catalyst activity for a long time is very important. Principal mechanisms of catalyst deactivation are loss of surface area due to fly-ash and ammonium bisulfate deposition; chemical deactivation by alkali or alkaline earth oxides, sulfur oxides, or heavy metal compounds; hydrothermal

sintering; and abrasion by fly-ash.

Simultaneous removal of SO_2 and NO_x using a regenerable solid sorbent will constitute an important improvement over the use of separate processes for the removal of these two pollutants from stack gases and possibly eliminate several shortcomings of the individual SO_2 and NO_x removal operations. This process will allow simple and reliable cleanup of large volumes of stack gases at a competitive cost; produce a concentrated stream of SO_2 which can easily be converted into valuable by-products; be compatible with existing power generation plants; and essentially eliminate the waste materials generated in some other sulfur removal processes. Department of Energy's Pittsburgh Energy Technology Center (PETC) has been involved with the development of a regenerative fluidized bed process using copper oxide-impregnated alumina spheres for simultaneous removal of SO_2 and NO_x since late 1960's. These efforts have been summarized by Yeh et. Al^(1,2). This process is expected to operate around 400°C . Another copper oxide based process is the UOP/Shell Process which uses a cyclic fixed-bed contactor. The advantages of the fluidized-bed design over a fixed-bed contactor were given as the elimination of the need for large diameter valves for the isolation of the reactor from the regenerator; constant flow of regenerator off-gas; and the elimination of the possibility of the plugging of the bed with fly-ash. Disadvantages of the fluidized-bed reactor are the relatively higher pressure drop and sorbent attrition.

More recent studies at PETC considered cerium oxide as an alternate sorbent to CuO ^(3,4). Ceria improves the resistance of the alumina support to thermal sintering and produces a regeneration off-gas stream that can be easily converted to elemental sulfur. It has a potentially higher sulfur capture capacity than copper. It is readily available at a moderate cost. Although it is more expensive than copper oxide, since the cost of metal oxide is a small fraction of the total sorbent cost, this may not be a significant factor.

An overview of the relevant information available in the literature is given below. More detail can be found in Sections 1, 2, 3, 4 of Appendix B.

I.A. Background Information

I.A.1. Copper Oxide-Based Sorbents for Combined SO_2/NO_x Removal

The reaction of copper oxide with SO_2 is usually written as:

In this reaction copper catalyses the formation of SO_3 and subsequently serves as a sorbent for it. The sulfation of alumina supported copper oxide is more complicated because as indicated by recent studies, the alumina support is directly involved in the sulfur removal process. Earlier work by Friedman et al.⁽⁵⁾ has indicated that for alumina support having a surface area of $200 \text{ m}^2/\text{g}$ and for copper loadings of less than 8%, copper was present not as crystalline CuO or CuAl_2O_4 but as a less well

defined entity. This observation was later confirmed by Strohmer et al.⁽⁶⁾. In PETC, Pollack et al.⁽⁷⁾ made an extensive analysis of fresh and used alumina-supported copper oxide sorbents using various methods of analysis. They used a sorbent containing 7.2 wt % Cu on alumina with a surface area of 230 m²/g which decreased to 190 m²/g upon regeneration. This roughly corresponds to a monolayer of copper. Their results indicate that the fresh sorbent is something other than crystalline CuO/alumina and that used sorbent is not CuSO₄/alumina. For copper loadings in excess of about 10% Cu on 200 m²/g alumina (monolayer coverage of sorbent with Cu) crystalline CuO appears on the surface and this is reported to cause a significant reduction in the structural strength of the sorbent during the sulfation-regeneration cycle⁽²⁾.

Centi et al.⁽⁸⁾ have made an extensive investigation of the CuO/alumina sorbents. During their thermogravimetric analysis they obtained S/Cu ratios in excess of 1 at temperatures above 275°C indicating direct participation of support in sulfur capture. Basing on their FTIR results they suggest the following mechanism for the sulfation of the sorbent: First SO₂ interacts with copper oxide sites forming SO₃ which subsequently reacts with a copper site forming copper sulfate surface species and deactivates the site. If neighboring support sites are present, the sulfate group can be transferred to the support and the site can be reactivated by the oxygen in the gas stream. Their

kinetic analysis show that since the sulfation rate slows down rapidly after an initial sharp increase, increasing the number of initial active sites will be more beneficial than increased residence times for achieving maximum sorbent utilization.

Centi et al.⁽⁸⁾ have also investigated the regeneration of sulfated copper oxide sorbents. Their results show that the regeneration process is more complicated than indicated by

The copper formed will immediately oxidize to CuO in the presence of oxygen. The temperature programmed reduction studies showed that the reduction of copper sulfate started in the range 300°C - 350°C producing SO₂. An autocatalytic effect was observed. Above 425°C H₂S appeared in the gas possibly due to reactions of CuS and/or Al₂(SO₄)₃. When methane was used for regeneration no H₂S was observed and the reduction occurred at higher temperatures. These results of Centi et al. suggest the presence of different sulfate species with different reducibilities. The presence of less reducible copper sulfate increases the N₂O formation thus reducing the NO_x removal efficiency. Higher temperatures decrease the formation of this type of sulfate species.

Harriott and Markussen⁽⁹⁾ investigated the regeneration kinetics of CuO/alumina sorbents and obtained the kinetic parameters for regeneration with methane. They found that the regeneration of the sorbent is strongly inhibited by the product gases, especially by SO₂. This is possibly due to the

competitive adsorption of product and reactant gases on the sorbent surface. The presence of copper oxides in the sulfated sorbent leads to the rapid formation of CuSO_3 and Cu_2SO_3 . The reduction of these with methane are limited to low conversions by equilibrium. This may create problems especially if the regeneration is performed in a moving bed by lowering the exit SO_2 concentration and creating a pinch in the reactor with zero or very low regeneration rate.

The interaction of sulfated CuO /alumina sorbents with ammonia has been investigated by Centi et al.⁽⁸⁾ Ammonia is the reactant introduced into the reactor for partial reduction of nitrogen oxides. The reactions

are catalyzed by the sulfated sorbent. The results of their TGA analyses show that ammonia is adsorbed on the sulfated sorbent in the temperature range 200°C to 275°C . It, then, forms ammonium bisulfate if sufficient time is allowed. At temperatures above 350°C evaporation of ammonium bisulfate causes sulfur loss decreasing S/Cu ratio. These results indicate that since NO_x conversion rate is very fast short contact times will reduce the ammonium bisulfate formation and sulfur loss. It was suggested that a suitable pore distribution in the sorbent may also control the ammonium bisulfate formation.

Pittsburgh Energy Technology Center has been involved in the

development of a regenerative process based on supported copper oxide since late 1960's. The process was first tested in a fixed bed reactor using copper -impregnated alumina spheres containing 6.3% copper by McCrea et al.⁽¹⁰⁾ The same sorbent was later used in fluidized bed reactors which included injection of ammonia for the simultaneous removal of NO_x ^(11,1). Yeh et al.⁽¹⁾ reported SO_2 and NO_x removal efficiencies in excess of 90%. In these fluidized bed tests the regeneration was done in a fixed bed. In another DOE sponsored study by Williamson et al.⁽¹²⁾, a continuous moving bed regenerator in conjunction with a smaller fluidized bed reactor was used. They reported conversions less than about 50% in the regenerator possibly due to low methane conversions and presence of copper oxides in the sulfated sorbent as discussed above.

I.A.2. Ceria-Based Sorbents for Combined SO_2/NO_x Removal

Due to the interest in ceria as a constituent of catalysts for the control of automobile emissions, the structure of alumina supported CeO_2 have been extensively investigated. Shyu et al.⁽¹³⁾ reported the existence of three phases on $\text{CeO}_2/\text{Al}_2\text{O}_3$: A dispersed phase that they called the CeAlO_3 , small CeO_2 crystals that appeared when the Ce loading is less than 2.8 mmol/m^2 (this corresponds to the saturation of alumina surface with Ce), and large CeO_2 particles (about 20 nm in size) when the Ce loading is above this value. Ceria in the CeAlO_3 precursor and small CeO_2

can be transformed into CeAlO_3 upon reduction in hydrogen at temperatures above 600°C .

Hedges and Diffenbach⁽³⁾ at PETC have investigated the sulfation and regeneration behavior of promoted and unpromoted $\text{CeO}_2/\text{Al}_2\text{O}_3$ sorbents. They found that the reactivity of these sorbents are comparable or slightly higher than that of copper oxide based sorbents, and that they can be regenerated in hydrogen or methane (at a higher temperature) with complete removal of sulfur. No loss of reactivity was observed over 4 cycles of operation. The operating temperature with ceria sorbents was 600°C compared to 400°C for copper oxide sorbents. They reported that silica offered no advantage over alumina as a support, addition of MnO_x or CoO_x to the sorbent did not improve reactivity, and potassium-modified sorbents exhibited up to 20% higher sulfur capture capacity at comparable metal loadings than the unpromoted ceria sorbents.

Hedges and Yeh⁽⁴⁾ studied the kinetics of SO_2 absorption by alumina supported ceria using thermogravimetric analysis. They reported that the absorption kinetics of SO_2 can be represented by a simple model which is first order with respect to SO_2 partial pressure and first order with respect to the fraction of unreacted CeO_2 on the sorbent.

$$k'P_s t = a_c \ln[a_c / (a_c - x_c)] \quad (4)$$

where $k' = k a_c$, k is the rate constant defined by $da_c/dt = k P_s a_c$, P_s is the partial pressure of SO_2 , a_c is the initial fraction (or

percentage) of cerium on the sorbent, and x_c is the fraction (or percentage) of cerium oxide that has been consumed at time t . An Arrhenius law type temperature dependence

$$k' = A \exp(-E/RT) \quad (5)$$

was assumed for k' . The experimentally determined values are

$$E = 12 \text{ kJ/mol and } A = 0.076 \text{ \%Ce.s}^{-1}.\text{kPa}^{-1}.$$

Hedges and Yeh⁽⁴⁾ have also reported X-ray diffraction, X-ray photoelectron spectroscopy and FTIR studies of sulfated sorbents. They suggested that upon exposure to flue gas, CeO_2 is converted to an amorphous or highly dispersed sulfate. The fresh and regenerated sorbents were found to contain CeO_2 and the regenerated sorbent was found to contain small amounts of sulfate but no detectable sulfide. The fully sulfated sorbent was found to contain predominantly Ce(III) . As a result, they suggested the use of

as the sulfation reaction.

I.A.3. Modeling of Moving Bed Reactors

Various gas-solid contacting arrangements are possible in a moving bed reactor:

1. Parallel flow of gas and solid,
2. Countercurrent flow of gas and solid, and
3. Cross flow of gas and solid.

A review of the moving bed literature and a general moving bed reactor model is discussed by Doraiswamy and Kulkarni⁽¹⁵⁾. Solids conversion in an isothermal moving bed is described by

$$\frac{D_s A_c \rho_s (1-\varepsilon)}{M_s} \frac{d^2 x}{dz^2} - \frac{F_s \rho_s}{M_s} \frac{dx}{dz} - R_A A_c = 0 \quad (7)$$

where D_s is the effective axial dispersion coefficient of solid in bed, A_c is the cross sectional area of the bed, ρ_s is the solid density, ε is the bed void fraction, M_s is the molecular weight of solid, x is the conversion of solid, z is the axial direction, F_s is volumetric flow rate of solid, and R_A is the rate of reaction. The change of the concentration of species A in the gas phase is given by

$$\frac{D_g A_c \rho_g \varepsilon}{M} \frac{d^2 C_A}{dz^2} - \frac{F_g \rho_g}{M} \frac{dC_A}{dz} - R_A A_c = 0 \quad (8)$$

where D_g is the effective axial dispersion coefficient of the gas, ρ_g is the gas density, C_A is the concentration of species A in gas, M is the average molecular weight of gas, and F_g is the volumetric flow rate of gas. The boundary conditions at the reactor inlet and outlet are

$$@z=0 \quad x = x_0 + \frac{D_s A_c (1-\varepsilon) dx}{L F_s dz} \quad (9a)$$

$$@z=0 \quad C_A = C_{A0} + \frac{D_s A_c \varepsilon}{L F_s} \frac{dC_A}{dz} \quad (9b)$$

$$@z=L \quad \frac{dx}{dz} = \frac{dC_A}{dz} = 0 \quad (9c)$$

where L is the total reactor length and subscript 0 indicate initial values.

This model assumes isothermal steady state conditions, no change in the radial direction, negligible mass transfer across gas-solid interface, and the co-current movement of the gas and solid phases. For other contacting arrangements, appropriate changes in the boundary conditions and in the sign of the flow term are required. This model has been solved by Hartman et al.⁽¹⁵⁾ for the removal of SO₂ from flue gases using calcium sulfate and sodium sulfide particles. Solutions for a counter current arrangement have been obtained by Evans and Song⁽¹⁶⁾. The design of a moving bed adsorber operating in cross flow mode has been discussed by Larsen and Pilat⁽¹⁷⁾.

A simple way to model a cross-flow moving bed reactor is to

consider it as a vertical stack of differential reactors. The inlet SO_2 concentration to each differential reactor will be the same. The residence time of the sorbent in the reactor for each differential reactor will be a function of the vertical location of the reactor and the sorbent flow rate. Therefore, the average outlet SO_2 concentration can be obtained from the time-averaged integral of the breakthrough curve. This method was used by TECOGEN to model the sulfation and regeneration reactors and is discussed in more detail in Appendix A Section 8.0.

II. DESCRIPTION OF THE PROJECT

II.A. Project Objectives

The objectives of this project were:

1. To obtain a rate expression for the sulfation and regeneration of alumina supported CeO_2 sorbents,
2. To determine the effects of ammonia on the sulfation of the sorbent,
3. To determine the effects of fly ash on the sulfation and regeneration of the sorbent,
4. To model the sulfation and regeneration reactors for a commercial scale combined SO_2/NO_x removal facility based on $\text{CeO}_2/\text{Al}_2\text{O}_3$ sorbent.
5. To study the economics of the ceria process and compare it to that of the copper oxide process.

II.B. Description of Project Tasks

The investigation has been planned so that its results will complement those in literature and eventually can be used for the design of industrial equipment. To elucidate the plan of study, the work to be undertaken was categorized as follows:

- Task 1. Sorbent preparation and characterization
- Task 2. Investigation of the kinetics of sulfation and regeneration of the ceria sorbent.
- Task 3. Investigation of the effect of ammonia concentration on the sulfation of ceria sorbent.
- Task 4. Investigation of the effect of the fly-ash on the sulfation and regeneration of ceria sorbent.
- Task 5. Modeling of sulfation and regeneration reactors; evaluation of the ceria-based flue gas cleanup process for industrial application.

III. SORBENT PREPARATION AND CHARACTERIZATION

Cerium oxide sorbents were prepared by the impregnation of an alumina support. It has been observed by previous investigators⁽³⁾ that different precursor salts for cerium showed little or no difference in sorbent capacity, but that a slightly higher rate of SO₂ uptake was obtained for sorbents prepared using ceric ammonium sulfate as the precursor salt. Therefore, it is decided to use a single cerium salt, namely ceric ammonium nitrate [Ce(NH₄)₂(NO₃)₆] in the preparation of the sorbents.

In a previous work done by DOE, alumina supports from Davison and UOP were employed^(3,18). It was decided to use this same type of support so that the effect of support type will not be a factor in our results. However, both companies were reluctant to supply the alumina support to us. UOP supplied some limited samples with restrictions on the type of analysis we could make and what results we could disclose. Davison has declined to supply any samples. Therefore, we have obtained 1/16 and 1/8 in. alumina spheres from ALCOA.

Sorbent samples were prepared by using both ALCOA and UOP alumina at different ceria loadings. Variations have been made in the preparation of samples by washing the alumina samples by different methods. It was decided to wash the alumina in order to reduce the powdery portion of ALCOA alumina. The following procedure was used for sorbent preparation:

1. Dissolve the required amount of cerium salt in distilled water: Ceric ammonium nitrate $[(\text{NH}_4)_2\text{Ce}(\text{NO}_3)]$ was used as the source of cerium. The amount of distilled water was just enough to wet the alumina. This was determined experimentally by wetting weighed amount of the ALCOA and UOP alumina particles. This was 14 cc and 18 cc for ALCOA and UOP aluminas, respectively.

2. Introduce the support into the cerium salt solution and mix:
Two types of support were used:

- i) ALCOA alumina (CSS 200 1/16"): The specifications of this alumina is given by the manufacturer as follows:

Apparent bulk density = 27- 52 lb/ft₃

Composition: Aluminum Oxide: 90 - 95 % (max: 99 %)

Sodium Oxide : 0.05-0.5 %

Silicon Oxide : 0.01-0.2 %

Iron Oxide : 0.03-0.1 %

Diameter = 1/16"

ii) UOP alumina (SAB-2 Catalyst):

The specifications of this alumina is given by the manufacturer as follows:

Apparent bulk density = 31.2 lb/ft₃

Composition: Aluminum Oxide: 100 %

Diameter = 0.063"

The ALCOA alumina was very powdery. Therefore it was washed by different procedures, and each one was used to prepare sorbents so that the effect of this variable on the properties of the resulting sorbents may be investigated. The washing methods used were:

- a) Wash alumina with acetone in a beaker 4 times; sieve each time; rinse on the sieve with acetone the last time; and leave it overnight in the oven at 120°C.
- b) Wash alumina with distilled water; vaporize the water on a hot plate; then repeat the same procedure as that used in (a). During vaporization on the hot plate, it was observed that there was a lot of powder in the water; and no gelling occurred during heating. The amount of

powder washed out was 0.6132 g from 15 grams of alumina, which is about 4%.

- c) Wash alumina with distilled water; and then repeat the same procedure as that used in (a).

UOP alumina has also been washed by method (a).

3. Put the impregnated alumina in the oven for drying; mix frequently; and leave in the oven overnight at 120°C.
4. Calcine the dried sorbent in air at 650°C for six hours: For this procedure, a calcination reactor setup has been built. It comprised of a 1/2" stainless steel tube as the calcination reactor which has been placed in a muffle furnace. An air flowrate of 50 cc/minute was employed. Some of the sorbents were calcined with N₂ under, otherwise, similar conditions mentioned above.

Sorbents containing 4, 8, and 12% cerium nominally, were prepared using ALCOA alumina. They were analyzed for their cerium content immediately to determine the cerium loading attained. Based on these measurements some more sorbents were prepared. Some of these sorbents are presented in Table 1. Unfortunately, toward the end of the project period, when we were investigating the effect of ceria content, the results indicated the possibility of significant error in the measurement of the ceria content of the prepared sorbents. Cerium mass fractions measured by a different laboratory are shown in parenthesis in Table 1.

The sorbents are characterized by the following methods:

1. Density measurements by helium pycnometry: The true density of the sorbents were determined using the MULTIPYCNOMETER manufactured by the Quantachrome Company.

Table 1. PREPARED SORBENTS

Sorbent	Nominal Cerium Loading, %	Actual Cerium Loading, %	Washing Procedure	Calcination Gas	Comment
ALCOA16-CE4-VI	4	4.39 (6.55)	(c)	Air	Incipient wetness
ALCOA16-CE8-II	8	7.64 (15.8)	(c)	Air	Incipient wetness
ALCOA16-CE8-III	8	7.04	(c)	Air	Incipient wetness
ALCOA16-CE12-I	12	9.28 (20.1)	(c)	Air	Incipient wetness
ALCOA16-CE12-II	12	13.2	(c)	Air	Incipient wetness
ALCOA16-CE12-III	12	14.7	(c)	Air	Incipient wetness
UOP16-CE4-III	4	3.13	(c)	Air	Incipient wetness
UOP16-CE4-IV	4		(c)	Air	Incipient wetness
UOP16-CE8-I	8		(c)	Air	Incipient wetness

2. Surface area measurements by nitrogen adsorption: The QUANTASORB surface area analyzer has been used to determine the surface area of the prepared sorbents. A gas mixture containing 30% (molar) nitrogen in helium is used as the adsorbate. The single point BET method rather than the multipoint method was used. This decision was based on the fact that the intercept of a BET plot is generally small when compared to the slope and can be neglected.

3. Porosity measurements by mercury intrusion: The Quantachrome AUTOSCAN-33 porosimeter was employed to measure the pore volumes of the solid samples by mercury intrusion method.

4. Determination of the cerium loading by atomic absorption measurements These measurements were done by our industrial partner Malcolm Pirnie, Inc. (MP). Method of digestion for these analyses was hot nitric acid and method of analysis was by ICP. Although we have requested an estimate of the error involved in these analyses, we could not get one. In the meantime we proceeded with our experimental program. When we analyzed our results with sorbents containing different amounts of ceria, we noticed some inconsistencies as described later in the report. At that time we decided to have some independent confirmation of ceria contents. With the remaining funds we had six sorbent samples analyzed for cerium content by the Jennings Laboratories, Inc. (JL) of Virginia Beach, VA. They have provided us with the results of duplicate and replicate analyses which indicated an error of less than 10%. Cerium content indicated by these analyses (shown in parenthesis in Tables 1 and 2) are much higher than those reported by Malcolm Pirnie. Our discussions with Jennings Laboratories led us to conclude that the lower results of Malcolm Pirnie may be due to incomplete digestion. Unfortunately by the time we got the new results it was too late to change the sorbent used and redo all the calculations.

5. Measuring the change in mass during calcination of prepared sorbents in air and nitrogen in a thermogravimetric analyzer: For this purpose, a CAHN Instruments TG-121 system is used to record the weight of the sorbent as a function of time as it undergoes calcination under a nitrogen or air atmosphere. In these runs, about 30 mg of the uncalcined sorbent was placed in a quartz pan. Helium at a flow rate of 79 cc/min was passed through the balance chamber as the purge gas, while nitrogen or air at a flowrate of 77 cc/min flowed through the 1" quartz reactor tube as the calcining gas.

The results of physical characterization experiments are summarized in Table 2.

The main conclusions from Table 2 can be summarized as follows:

1. The more recent atomic absorption measurements indicated that the original cerium measurements conducted by Malcolm Pirnie were not dependable and the prepared sorbents had more cerium than the intended amount especially at higher loadings.
2. For the sorbents prepared with the ALCOA alumina, as the cerium loading increases, the pore volume of the sorbent decreases, indicating that the smaller pores are blocked by cerium. This last fact is evidenced by the increase in the mean pore radius of the micropores. The cerium loading for monolayer coverage of the particular alumina support we have used is about 10 wt% cerium. As the monolayer coverage is

Table 2. PHYSICAL CHARACTERISTICS OF SORBENTS

Solid	Ce Loading % by mass	Surface Area, m ² /g	Intruded Hg Volume cm ³ /g	Mean Pore Radius, mm	True Solid Density, g/cm ³	Porosity %
ALCOA Alumina	none	219	0.5365	0.00324 & 0.404	2.819	0.602
UOP Alumina	none	147	0.8092	0.0085	2.787	0.6928
ALCOA-CE4-I	0.56				3.2337	
ALCOA-CE4-II	0.37		0.7746	0.00424 & 0.5	3.4700	0.7288
ALCOA-CE4-III	0.74	139	0.7467	0.0044 & 0.47	3.1841	0.7039
ALCOA-CE4-IV	1.59 (3.2)	132	0.7145	0.00444 & 0.5	3.2596	0.6996
UOP-CE4-I	1.08	120	0.8282	0.01144	3.0731	0.7179
UOP-CE4-II	1.32	114	0.8232	0.01133	3.2274	0.7265
ALCOA-CE4-V	4.58 (6.8)	93	0.71	0.00644 & 0.5	3.2382	0.6969
ALCOA-CE4-VI	4.39 (6.55)	111	0.6307	0.0045 &0.65	3.2758	0.6738
ALCOA-CE8-II	7.64 (15.8)	97	0.5727	0.0038, 0.0067, 0.49	3.3931	0.6602
ALCOA-CE8-III	7.04	107	0.6039	0.004, 0.0063, 0.45	3.5669	0.6569
ALCOA-CE12-I	9.28 (20.1)	81	0.3121	0.0045, 0.0072, 0.45	3.5738	0.5270
ALCOA-CE12-II	13.2	100	0.4766	0.0035, 0.0055, 0.45	3.7122	0.6389
ALCOA-CE12-III	14.7	64	0.438	0.0035, 0.008, 0.5	3.8265	0.6260
UOP-CE4-III	3.13	122	0.7745	0.012	3.1076	0.7065
UOP-CE4-IV		115	0.8007	0.012	3.2924	0.7250
UOP-CE8-I		92	0.6890	0.012	3.197	0.6878

approached (or exceeded if JL results are used) the effect of cerium loading on porosity becomes more significant. With the sorbents prepared on the UOP alumina, we do not have enough samples and measurements to reach such conclusions.

Another interesting observation is that the pore volumes of the cerium-loaded sorbents are higher than those of the fresh alumina samples probably due to the calcination step during preparation.

3. The surface areas of the sorbents decrease almost linearly as the cerium loading increases. This is due to the fact that small pores are blocked by cerium as mentioned above.

The main conclusions from the thermogravimetric analysis may be summarized as follows:

1. Calcination in the air and nitrogen produce the same product. For example, Figures 3a and 3b exhibit the same final conversion for the calcination of ALCOA 16-CERIA4-IV in the presence of nitrogen and air, respectively. This may be due to the fact that there is some oxygen in the medium during the decomposition of the ammonium ceric nitrate:

2. There is a discrepancy of about 12% (7.5% with the JL cerium measurement) between the experimental results obtained from the thermograms compared to the theoretical mass balance calculations for the systems under study. This is accounted for by the possible existence of moisture on alumina and water

of hydration formed during the impregnation of the cerium salt on alumina.

3. The results obtained from TGA are reproducible as can be observed from Figures 1 - 4.

IV. STANDARD SULFATION-REGENERATION RUNS WITH PELLETS

The standard sulfation-regeneration runs with 1/16-in sorbent pellets were done at the following settings:

1. Standard sulfation-regeneration experiments on ALCOA16-CE4-VI for 6 cycles (TESTS 5-10):

The sulfation temperature was 600°C and the regeneration temperature was 600°C.

Sulfation gas composition:

0.3% SO₂, 3% O₂, 14% CO₂, 4% H₂O, balance N₂.

Regeneration gas composition:

H₂ + N₂ : hydrogen composition is varied.

Gas flow rate: 200 cc(NTP)/min

The thermograms from these experiments were presented in Figures 4-10

2. Standard sulfation-regeneration experiments on UOP16-CE4-III for 4 cycles (TESTS 11-14): The experimental conditions were kept the same as above. The thermograms for these experiments were presented in Figures 11-14.

FIGURE 1. Thermogram for Copper Sulfate Decomposition

FIGURE 2. Thermogram for Copper Sulfate Decomposition

FIGURE 3. Thermogram for the Calcination of ALCOA 16-CE4-IV in Nitrogen

FIGURE 4. Thermogram for the Calcination of ALCOA 16-CE4-IV in Air

FIGURE 6. Standard Sulfation - Regeneration TEST6.
Regeneration Gas : H_2 : 100% ; Sorbent : ALCOA 16-CE4-VI.

FIGURE 7. Standard Sulfation - Regeneration TEST7.
Regeneration Gas : H_2 : 75%, N_2 : 25% ; Sorbent : ALCOA16-CE4-VI.

FIGURE 8. Standard Sulfation - Regeneration TEST8.
Regeneration Gas : H_2 : 50% , N_2 : 50% ; Sorbent : ALCOA16-CE4-VI.

FIGURE 9.

FIGURE 10. Standard Sulfation - Regeneration TEST10.
Regeneration Gas : H₂ : 12.5% , N₂ : 87.5% ; Sorbent : ALCOA16-CE4-VI.

FIGURE 11.
Standard Sulfation - Regeneration TEST11.
Regeneration Gas : H₂ : 12.5% , N₂ : 87.5% ; Sorbent : UOP16-CE4-III.

FIGURE 12. Standard Sulfation - Regeneration TEST12.
Regeneration Gas : H₂ : 25% , N₂ : 75% ; Sorbent : UOP16-CE4-III.

FIGURE 14.
Standard Sulfation - Regeneration TEST14.
Regeneration Gas : H₂ ; 75% , N₂ : 25% ; Sorbent : UOP16-CE4-III.

FIGURE 13. Standard Sulfation - Regeneration TEST13.
Regeneration Gas : H₂ : 50% , N₂ : 50% ; Sorbent : UOP16-CE4-III.

IV.A. Sulfation Experiments

The thermograms were evaluated by calculating the sulfur/cerium ratio (S/Ce) and the conversion of cerium oxide due to sulfation (X_s). In these calculations, the following reaction was assumed to take place on the sorbent based on the results cited in the literature^[1,2]:

The following equations are used to calculate S/Ce and X_s :

$$\frac{S}{\text{Ce}} = 1.5 \frac{\Delta m}{112 n_0} \quad (11)$$

$$X_s = \frac{\Delta m}{112 n_0} \quad (12)$$

where n_0 = initial number of moles of CeO_2 , mmol;

m = mass of sorbent at any time, mg;

Δm = $m - m_0$, mg;

m_0 = initial mass of sorbent, mg;

S/Ce = atomic ratio of sulfur to cerium.

The S/Ce ratios are presented on Figure 15 for the tests 5-10. The main conclusions drawn from these experiments are:

1. The sorbent shows higher sulfation capacity in the first cycle compared to the capacity in the subsequent cycles.
2. After the first cycle, the sorbent maintains its capacity through the subsequent five cycles.

Figure 15. S/Ce Ratios for 4.39% Ce (MP) on ALCOA Alumina T=873K, SO₂=0.3%

3. When the results of Malcolm Pirnie cerium analyses are used, the sorbent exhibits a capacity that is higher than that corresponding to the theoretical value calculated according to the stoichiometry of the reaction of Equation (6). This is attributed to either the interaction of cerium with alumina or the additional capacity supplied by the alumina itself.

To find the sulfur capacity of alumina alone, it was decided to do standard sulfation tests on pure alumina. The results for conversion are presented in Figure 16. These results indicate that a very low capacity for sulfur dioxide removal by alumina on its own. Therefore it was concluded that the presence of CeO_2 , which catalyzes the oxidation of chemisorbed SO_2 , is necessary for the formation of sulfate species linked to the aluminum atom.

On the other hand if the cerium analyses of the Jennings Laboratories are used, the S/Ce ratios shown in Figure 15 need to be multiplied by 0.67 and indicate over 100% sulfation for the first cycle and about 95% sulfation of ceria within an hour of sulfation for the subsequent cycles. We can again invoke the deep sulfation of alumina to explain the over 100% sulfation observed during the first cycle. The behavior during subsequent cycles may be attributed to the difficulty of the regeneration of aluminum sulfate species.

Figure 17 presents similar results for the sorbent prepared using the UOP alumina.

Figure 16. Comparison of 4.39% Ce Sorbent with Alumina $T=873$ K; $SO_2=0.3\%$

FIGURE 17. S/Ce Ratios for 3.13% Ce (MP)
on UOP Alumina T= 873 K; SO₂=0.3%
Standard Conditions

IV.B. Regeneration Experiments

During the regeneration of the experiments discussed in the previous section (Tests 5-14), the partial pressure of hydrogen has been varied in order to obtain data to determine the regeneration order with respect to hydrogen. The hydrogen mole fraction in the regeneration gas was varied between 0.125 and 1.0. It was observed that reproducible regeneration was realized in all of these experiments as apparent from Figures 15 and 17. The initial rate data for regeneration from these experiments were fitted by the linear least squares method to obtain the order of the reaction with respect to hydrogen according to the following equation:

$$R_{R_0} = k_R (P_{H_2})^n \quad (13)$$

Linearizing this equation gives:

$$\log(R_{R_0}) = \log(k_R) + n \log(P_{H_2}) \quad (14)$$

where

R_{R_0} = initial regeneration rate, mg/s,

k_R = rate constant for regeneration at 873 K,

P_{H_2} = partial pressure of hydrogen,

n = order of regeneration reaction with respect to hydrogen.

The order n was determined to be 0.5.

V. RESULTS OF RUNS WITH SORBENT PELLETS

V.A. Experiments with Standard TGA Configuration

Further tests were undertaken on a sorbent with 4.39% (6.55% by JL) cerium on ALCOA alumina to obtain the activation energy and the order with respect to sulfur dioxide of the sulfation reaction. Fresh sorbents were loaded at tests 20, 26 and 32. In the tests 32-48, the regeneration has been done with pure hydrogen to ensure complete regeneration of the sorbent. The results from these tests are summarized below:

1. Figure 18 presents the performance of the sorbent at different cycles and tests at 873 K and a concentration of SO_2 of 3000 ppm (the S/Ce ratios in this figure need to be multiplied by 0.67 to obtain the results based on JL analysis). As has been mentioned previously, the sorbents exhibit higher sulfation capacity in the first cycle. In the subsequent cycles, the capacity decreases and stabilizes at a lower level (See also Figure 15). However, this factor does not affect the initial rate data as may be observed from Figure 18.

2. Figures 19, 20, and 21 show the effect of SO_2 concentration on the sorbent capacity at 873 K, 773 K, and 923 K, respectively. Concentration of SO_2 was varied at different temperatures in order to find whether there is any dependency of the sulfation reaction order with respect to SO_2 on temperature.

Due to the effect of the concentration of SO_2 on the rate of sulfation, the sorbent capacity becomes appreciably higher, at the

Figure 18. Effect of Cycling on 4.39% Ce (MP) on ALCOA Alumina. T=873 K; SO₂=0.3%

Figure 19. Effect of SO₂ composition
4.39% Ce (MP) on ALCOA Alumina. T=873 K

Figure 20. Effect of SO₂ Concentration.
4.39% Ce (MP) on ALCOA Alumina. T=773 K

S/Ce Ratios for SO₂ Uptake by 4.39% Ce on ALCOA Alumina Sorbent

Figure 21. Effect of SO₂ Concentration.
4.39%Ce (MP) on ALCOA Alumina. T=923 K;
Flow Rate= 200 sccm

reaction times used, with higher SO₂ concentrations at all the temperatures. These figures also exhibit the same behavior with respect to cycling as discussed above; that is, the sulfation activity at the first cycle is high, but it stabilizes in the subsequent cycles, and does not deteriorate appreciably even in 17 cycles (Tests 38 and 42 in Figure 19).

The initial rate of sulfation data from these experiments were fitted by the linear least squares using the following equations:

$$R_{s_0} = k_s (P_{SO_2})^m \quad (15)$$

$$\log(R_{s_0}) = \log(k_s) + m \log(P_{SO_2}) \quad (16)$$

where R_{s_0} = initial sulfation rate, mg/s,
 k_s = rate constant for sulfation,
 P_{SO_2} = partial pressure of sulfur dioxide,
 m = order of regeneration reaction with respect to sulfur dioxide.

The regression results are as follows:

$$m = 1.05 \text{ at } 873 \text{ K,}$$

$$m = 0.948 \text{ at } 773 \text{ K, and}$$

$$m = 1.330 \text{ at } 923 \text{ K.}$$

The 95 % confidence intervals have not been calculated on these results; but it may be deduced that if all the data are pooled and regressed together, value of '1' will be in the confidence interval.

3. Figure 22 shows the effect of temperature on the sulfation capacity. In the 773-873 region, the sorbent capacity is comparable. This observation is very important from the point of view of industrial applications. The capacity decreases appreciably as the temperature decreases for temperatures lower than 773 K. The behavior of the sorbent capacity at 923 K is anomalous: it is even lower than the capacity at 673 K. The experiment at 923 K has been repeated several times to ensure reproducibility; this observation is reproducible. This behavior may be due to a chemical equilibrium limitation.

The initial sulfation rate data from these tests were fitted by the linear least squares method by using the Arrhenius relationship:

$$k_s = k_{s0} \exp(-E / RT) \quad (17)$$

where k_{s0} = preexponential factor,

E = activation energy, kJ/mol,

R = gas constant,

T = temperature, K.

Equation 17 has been linearized to give:

$$\ln(k_s) = \ln(k_{s0}) - \frac{E}{RT} \quad (18)$$

E was determined to be 7 kJ/mole by using the initial rate data at a SO_2 concentration of 3000 ppm. This value is very low for a

Figure 22. Effect of Temperature.
4.39% Ce (MP) on ALCOA Alumina. SO₂=0.3%

system governed by kinetic rate of a chemical reaction; it indicates external mass transfer limitations in the process. Thus, it was decided to change the reactant flow rate to investigate its effect on the rate.

4. Figure 23 presents the effect of reactant flow rate on the rate of sulfation. There is no change in the initial sulfation rate with a variation of flow rate; the difference in the sorbent capacity is due to the fact that test 26 is the first cycle in a series of tests. However, since the calculated activation energy suggests external mass transfer limitations, it is absolutely necessary to enhance the external mass transfer rate in order to generate intrinsic rate data. In addition to changing the reactant flow rate, one can enforce some changes to facilitate the contact with the external surface area. Thus, it was decided to make some changes in the experimental setup so that the reactant gas stream would be fed from the top of the TGA reactor. A piece of quartz wool was, also, placed in the pan so that all the sorbent particles will be effectively exposed to the reactant gas stream. Both of these changes will ensure better contact between the reactant gas stream and the sorbent particles, thus increasing the interfacial area and thus, the external mass transfer rate.

Figure 24 presents the impact of these changes on the initial sulfation rate and the sorbent capacity; the former has been enhanced appreciably by the recent changes while the latter remained the same as expected. Therefore, the experiments 20-48

S/Ce Ratios for SO₂ Uptake by 4.39% Ce on ALCOA Alumina Sorbent

Figure 23. Effect of Flow Rate.
4.39% Ce (MP) on ALCOA Alumina. T=923 K;
SO₂= 0.3%.

S/Ce Ratios for SO₂ Uptake by 4.39% Ce on ALCOA Alumina Sorbent

Figure 24. Effect of Flow Path.
4.39% Ce (MP) on ALCOA Alumina. T=873 K;
SO₂= 0.3%.

have to be repeated to obtain the intrinsic kinetics of the sulfation reaction.

5. Figure 25 presents the effect of water on the sulfation reaction. It has been reported in literature^(3, 4) that there is no effect of water on the rate of the sulfation reaction in the range of 4-18% (by mole) of water; however, since a different support has been used in the present study, we wanted to check whether this is the case for our sorbent too. Figure 25 exhibits that there is no effect of water vapor on the sulfation reaction.

V.B. Experiments with downflow of TGA gas

In these tests, same sorbent batch (4.39% cerium on ALCOA alumina) of 50 mg mass was used; it consisted of spherical particles of 1/16 inches. The sample was placed on quartz wool to spread it in order to enhance interphase mass transfer. Sulfation gas was composed of 0.3% SO₂, 14% CO₂, 3% O₂, 45% He, and the balance N₂. The regeneration of the sorbent between these tests was done at 873 K with a regeneration gas consisting of 55% H₂ and 45% He by volume. The gas flow was introduced from the top of the reactor tube in the TGA.

V.C. Effect of Cycling

Figure 26 shows the variation of the sulfur capture capacity of the sorbent with cycling. The sulfur capacity decreases by about 10% after the first cycle but the change becomes much smaller

Figure 25. Effect of Water
 T=873 K; SO₂=0.3%; H₂O=4%
 4.39% Ce (MP) on ALCOA Alumina

Figure 26. Effect of Cycling; Flowrate
 T=873 K; SO₂=0.3%; 1/16" particles
 4.39% Ce (MP) ALCOA Alumina.

in further cycling. The regenerated sorbents captured about 2 sulfur atoms for each cerium atom while this ratio is about 2.5 for the fresh sorbent (1.4 and 1.7, respectively if JL results are used). The results with Malcolm Pirnie analysis indicate contribution by the support to sulfur retention. Involvement of the support in the sulfation reaction mechanism has been investigated for Cu-based sorbents by Centi et al.^(19,20) A similar mechanism is expected for the sulfation of Ce-based sorbents. Since these sorbents are used at higher temperatures a larger contribution of the aluminum species to the formation of surface sulfate species is anticipated. Since run 69 B was done after the sorbent was exposed to a gas containing both ammonia and water, its relatively lower sorbent capacity may be partly due to the cumulative effect of ammonia and water.

V.D. Effect of Mass Transfer Limitations

To check the importance of external mass transfer resistance, the gas flow rate of the standard cycle was increased (Tests 56 and 64). The results of these tests are also presented in Figure 26. The initial rate increased by about 8% when the flow rate is doubled indicating some but not total mass transfer control at 873 K. Conversion versus dimensionless time plots were made for runs at 873 K and 673 K, and compared to the plots of the equations for mass transfer control, ash layer control and reaction rate control cases taken from Levenspiel⁽²¹⁾. These plots are shown in Figures

27 and 28. It appears that sulfation rate at 873 K is controlled mainly by external resistance to mass transfer while that at 673 K appears to be reaction rate controlled. Therefore, subsequent runs were made using sorbent particles obtained by crushing the pellets.

V.E. Effect of Temperature

Figure 29 shows the effect of temperature on the sulfur capacity. Even at 673 K, the sorbents can bind over 1.5 sulfur atoms per cerium atom (over one sulfur atom per cerium atom with the Jennings Laboratory analysis). The highest S/Ce ratios are obtained in the temperature range 773-873 K. The optimum operating temperature will be determined by the process economics. The tests performed at 673, 723 and 773 K were subsequently continued at 873 K. The results indicate that the sorbent capacity is determined by the chemical equilibrium at the prevailing temperature.

V.F. Effect of Water Vapor

Figure 30 shows that the sorbent performance is not affected by water in the absence of ammonia. However, the sorbent capacity is significantly reduced by water vapor in the reactants in the presence of ammonia (Figure 31). This may be due to the competitive adsorption of water on active sites.

V.G. Effect of Ammonia

From Figure 32 it appears that a small amount of ammonia is sufficient to cause about 10-15% reduction in sorbent capacity but

Kinetics of Sulfation Reaction (4.39% Cerium on ALCOA Alumina)

Figure 27. Kinetics of Sulfation Reaction
T=873 K; SO₂=0.3%; tau=436 s
4.39% Ce (MP) on Alumina; 1/16" spheres.

Figure 28. Kinetics of Sulfation Reaction
 $T=673\text{ K}$; $\text{SO}_2=0.3\%$; $\tau=3024\text{ s}$
 4.39% Ce (MP) Alumina; $1/16''$ particles.

Figure 29. Effect of Temperature
 SO₂=0.3%; no water; no NH₃; 1/16" spheres
 4.39%Ce(MP); all tests terminated at 873K

Figure 30. Effect of Water
 T=873 K; SO₂=0.3%; no NH₃;
 4.39% Ce on Alumina; 1/16" spheres

Figure 31. Effect of Temperature and H₂O
 SO₂=0.3%; NH₃=500 ppm; 1/16" spheres
 4.39% Ce on ALCOA Alumina

Figure 32. Effect of Ammonia
 T=873 K; SO₂=0.3%; no water;
 4.39% Ce (MP); 1/16" spheres

this effect does not seem to depend strongly on ammonia concentration. Since ammonia adsorption is not expected to be very significant at 873 K and ammonium bisulfate is not stable above 600 K⁽¹⁰⁾, further tests are needed to explain this effect. These results are also compared on Table 3.

TABLE 3. Effect of Temperature and Ammonia Concentration on S/Ce Ratio at 50 minutes.

SO₂=0.3%; no water; 1/16" particles.

Test #	Cycle #	Ammonia Concentration (ppm)	S/Ce at 50 minutes
T = 873 K			
52	4	0	2.085
56	8	0	1.960
64	16	0	1.857
57	9	250	1.858
63	15	350	1.810
58	10	500	1.923
T = 773 K			
53	5	0	1.988
61	13	250	1.673
62	14	500	1.543
T = 673 K			
51	3	0	1.498
59	11	250	1.336
60	12	500	1.388

VI. RESULTS WITH SORBENT PARTICLES

VI.A. Regeneration of Sulfated Sorbent

For the regeneration experiments, a large sample of sulfated sorbent was prepared. The ceria sorbent prepared previously (ALCOA16-CE4-VI) was crushed and sieved to the 90-150 mm, 75-90 mm, and <75 mm fractions. The experimental setup was modified by replacing the TGA reactor with a quartz tubular reactor which is of 1.5 cm ID in the middle, and 1 cm ID otherwise. The reactor is fitted with a quartz frit of 20 mm to hold a fixed bed of sorbent. This reactor was loaded with 0.5 g of the 90-150 mm fraction of the ALCOA16-CE4-VI sorbent, which was subsequently sulfated for seven hours with 400 cc/min of a sulfation gas of the following composition: 0.3% SO₂, 3% O₂, 14% CO₂, and 82.7% N₂. Then the reactor was cooled under a nitrogen atmosphere; and the sulfated sorbent was stored to be used for the regeneration experiments.

In the regeneration experiments to be performed in the TGA, it was decided to put some quartz wool into the pan in order to disperse the sulfated sample. However, this caused static in the TGA reactor. Static was eliminated by washing and it was decided to leave the quartz wool in the pan for the regeneration experiments.

VI.A.1. Regeneration with Hydrogen

Hydrogen was the first regeneration agent to be used. Due

to its low molecular weight, buoyancy effects were appreciable in the TGA. Therefore blank tests were run with no sorbent in the pan and thermograms were obtained for these runs in the TGA to be used for the correction of the buoyancy and gas switching effects.

The following procedure was used during the regeneration runs:

A 3.5 mg sample of the sulfated sorbent (ALCOA16-CE4-VI) was heated to the regeneration temperature under a nitrogen flow rate of 200 cc/min. After the heat-up period, time was allowed for the desorption of all adsorbed species. After the weight of the sample became reasonably constant, the reactant gases, consisting of hydrogen and nitrogen, were introduced into the TGA reactor by the switching valves. The sulfated sorbent was exposed to the regeneration gases until no further weight changes occurred. When the regeneration was complete, the system was cooled to room temperature under nitrogen flow.

The hydrogen concentration in the regeneration gases and the reaction temperature were the main variables used during the regeneration tests. The hydrogen concentration was varied between 10 and 75% (by mole), while the temperature range was 773 - 873 K.

Thermograms corrected for buoyancy effects were obtained by subtracting the blank runs from the test runs. To do this first both data are lightly smoothed. Then, the times for both runs

were matched at the tip of the small flow disturbance peak which occurred when the reactant gases were switched on. The corrected data were then obtained as the difference of the test run and the blank run data. The initial linear portion of the corrected regeneration weight versus time data was used to obtain the initial rate for the run.

VI.A.1.a. Data Evaluation

The regeneration data were evaluated using the following reaction stoichiometry:

The conversion of $\text{Ce}_2(\text{SO}_4)_3$ is calculated from the mass data as follows:

Cerium to alumina mass ratio in the original sample is

$$\frac{m_{\text{Ce}}}{m_{\text{Al}_2\text{O}_3}} = \frac{w_{\text{Ce}}}{1 - w_{\text{Ce}}} \quad (20)$$

where w indicates mass fraction. The cerium to alumina mole ratio is

$$\frac{n_{Ce}}{n_{Al_2O_3}} = \left(\frac{m_{Ce}}{m_{Al_2O_3}} \right) \left(\frac{M_{Al_2O_3}}{M_{Ce}} \right) \quad (21)$$

where M indicates the molecular weight. Then the mass of $Ce_2(SO_4)_3$ in the original sulfated sample becomes

$$m_{o,Ce_2(SO_4)_3} = \left(\frac{n_{Ce}}{n_{Al_2O_3}} \right) \left(\frac{m_{Al_2O_3}}{M_{Al_2O_3}} \right) \left(\frac{M_{Ce_2(SO_4)_3}}{2} \right) \quad (22)$$

The initial mass of the sulfated sample, m_o can be written using the following relationship:

$$m_o = m_{o,Ce_2(SO_4)_3} + m_{Al_2O_3} = \left[1 + 2 \left(\frac{n_{Al_2O_3}}{n_{Ce}} \right) \left(\frac{M_{Al_2O_3}}{M_{Ce_2(SO_4)_3}} \right) \right] (m_{o,Ce_2(SO_4)_3}) \quad (23)$$

Mass of sample, m , at any time during the reaction will be

$$m = m_o - x \left(\frac{m_{o,Ce_2(SO_4)_3}}{M_{Ce_2(SO_4)_3}} \right) (M_{Ce_2(SO_4)_3} - M_{Ce_2O_3}) \quad (24)$$

Therefore, the conversion of $Ce_2(SO_4)_3$ at anytime during regeneration becomes

$$x = \frac{(m_o - m)(M_{Ce_2(SO_4)_3})}{(m_{o,Ce_2(SO_4)_3})(M_{Ce_2(SO_4)_3} - M_{Ce_2O_3})} \quad (25)$$

Hence,

$$\frac{dx}{dt} = -\frac{(M_{Ce_2(SO_4)_3})}{(m_{o,Ce_2(SO_4)_3})(M_{Ce_2(SO_4)_3} - M_{Ce_2O_3})} \left(\frac{dm}{dt} \right) \quad (26)$$

The rate of the regeneration reaction, r , is written as

$$r = -k p_{H_2}^a c_{CS}^b \quad (27)$$

where k is the reaction rate constant and a and b are the reaction orders with respect to hydrogen and cerium sulfate, respectively. The subscript CS indicates $Ce_2(SO_4)_3$. Moles of cerium sulfate present at any time, can be written in terms of conversion

$$n_{Ce_2(SO_4)_3} = (1 - x) \left(\frac{m_{o,Ce_2(SO_4)_3}}{M_{Ce_2(SO_4)_3}} \right) \quad (28)$$

The reaction rate becomes

$$r = \frac{1}{m_o} \frac{dn_{\text{Ce}_2(\text{SO}_4)_3}}{dt} = -\frac{1}{m_o} \frac{m_{o,\text{Ce}_2(\text{SO}_4)_3}}{M_{\text{Ce}_2(\text{SO}_4)_3}} \frac{dx}{dt} \quad (29)$$

or , using equation (26)

$$r = \frac{1}{(M_{\text{Ce}_2(\text{SO}_4)_3} - M_{\text{Ce}_2\text{O}_3})} \left(\frac{dm}{dt} \right) \quad (30)$$

VI.A.1.b. Results and Discussion

The results from the regeneration tests are summarized below. Figure 33 shows the Arrhenius plot for the regeneration reaction with 50 % hydrogen (Equation 19). The activation energy is found to be 114 kJ/mol (27 kcal/ mol).

Figure 34 is the log-log plot of initial rate versus hydrogen mole fraction. The spread in data points at high hydrogen concentrations is mainly due to the errors introduced in accounting for the buoyancy effect during data analysis. The reaction order with respect to hydrogen is determined from the slope of this curve as 0.56. This fractional order can be explained by using Langmuir-Hinshelwood kinetics. For dissociative adsorption of hydrogen

$$r = \frac{k_2 P_{\text{H}_2}}{[1 + (K_1 P_{\text{H}_2})^{1/2}]^2} \quad (31)$$

Figure 33. Effect of Temperature on Regeneration Rate. H₂ mole fraction=0.5 4.39% Ce (MP) on ALCOA Alumina particles

Figure 34. Effect of H₂ Concentration on Reaction Rate. T= 873K; 4.39% Ce (MP) on ALCOA Alumina particles.

Equation (31) was linearized as shown in equation (32)

$$\sqrt{\frac{p_{H_2}}{r}} = \sqrt{\frac{K_1}{k_2}} \sqrt{p_{H_2}} + \frac{1}{\sqrt{k_2}} \quad (32)$$

and fitted to initial rate versus hydrogen fraction data using a linear regression software. The correlation coefficient for the fit is 0.95844 and the estimates for K_1 and k_2 are

$$K_1 = 9.23$$

$$k_2 = 1.17$$

The conversion versus time data are given in Figure 35. It is apparent that even with a regeneration gas containing 10% hydrogen 70% conversion is attained within 10 minutes. Figure 36 shows the effect of temperature on equilibrium conversion. This figure suggests that equilibrium conversion decreases with temperature. At 773 K the rate of reaction becomes so small that the curve for this temperature does not give any indication of equilibrium conversion.

If the reaction rate is first order with respect to the solid reactant conversion will change with time according to equation (33).

$$-\ln(1-x) = k_1 t \quad (33)$$

Figure 37 shows a plot of $-\ln(1-x)$ versus time. It can be seen from this figure that the reaction is first order with respect to

Figure 35. Effect of H₂ concentration on Regeneration; T = 873 K; 4.39% Ce (MP) on ALCOA Alumina particles.

Figure 36. Effect of Temperature on Regeneration; $H_2 = 50\%$; 4.39% Ce (MP) on ALCOA Alumina particles.

Figure 37. Regeneration Kinetics; T=873 K
4.39% Ce (MP) on ALCOA Alumina particles

solid reactant up to about 40 % conversion.

VI.A.2. Regeneration with Methane

The following procedure was used during the regeneration runs with methane:

The sulfated sorbent (3.5 mg of ALCOA16-CE4-VI) was heated to the regeneration temperature under a nitrogen flow rate of 200 cc/min. After the heat-up period, time was allowed for the desorption of all adsorbed species. After the weight of the sample became reasonably constant, the reactant gases, consisting of methane and nitrogen, were introduced into the TGA reactor by switching the valves. As will be discussed later during the regenerations with methane coke deposition was observed. This resulted in an initial mass decrease followed by a mass increase. The sulfated sorbent was exposed to the regeneration gases until a constant mass increase rate is obtained. After the regeneration was terminated, the system was cooled to room temperature under nitrogen flow.

The methane concentration in the regeneration gases and the reaction temperature were the main variables used during the regeneration tests with methane. The methane concentration was varied between 15 and 45% (by mole), while the temperature range was 873-943 K. Because the buoyancy effects are smaller for methane mixtures and considering the error introduced when a thermogram is subtracted from another, a different procedure was

used in the evaluation of methane regeneration data. It was observed that the transient flow disturbance and buoyancy effects existed within the first 60 seconds of the thermogram. For this reason, the initial rates were obtained by fitting a straight line to the mass versus time data starting after sixty seconds after gas switching. Data points were included until the correlation coefficient for the fit fell below 0.9950.

Additional runs were performed to investigate the effect of the regeneration agent, i.e. methane in this case, on the cyclic performance of the sorbent, because the previous runs on cyclic behavior were done using hydrogen during regeneration.

VI.A.2.a. Data Evaluation

The regeneration of alumina-supported ceria has been investigated by Shyu, et al.⁽¹³⁰⁾ They report that while below 600 K the formation of nonstoichiometric $\text{CeO}_{1.83}$ and $\text{CeO}_{1.72}$ is the most favorable reaction, above 800 K the formation of CeAlO_3 is a more favorable thermodynamic process. On the other hand, kinetically, reduction to CeAlO_3 requires temperatures higher than 873 K. According to these results both CeO_x and CeAlO_3 can exist at the temperatures used for regeneration experiments. This makes the interpretation of the regeneration data difficult and the XRD analysis of the reduced sorbents to identify the crystalline species a must. Since due to low metal content, the XRD results are not expected to be reliable, to find out which reduction

product is predominant some regeneration data were analyzed separately using Ce_2O_3 and CeAlO_3 as the reaction products. While the former gave reasonable results, the latter indicated conversions over 100 %. Therefore it appears that CeAlO_3 is probably not present in significant amounts. Therefore, for this report, the regeneration data using methane as the regeneration agent were evaluated using the following stoichiometry:

Elemental carbon formation is included in the reaction stoichiometry because significant coking of the sorbent was observed both visually and from the TGA results (Figures 38-40). The initial rate data were evaluated assuming that reaction (1) is the dominant reaction at the start of regeneration. The conversion data were obtained by assuming a constant rate for the second reaction. Thus, to obtain the mass of sorbent at any time, the amount of coke formed (obtained using the constant coking rate) is subtracted from the measured mass.

VI.A.2.b. Coking during regeneration with methane

The most significant observation during regeneration with methane is the formation of coke on the sorbent. This is indicated by a minimum in the observed mass during regeneration. If the sorbent was allowed to cool after regeneration under methane atmosphere, it was visually observed that the sorbent was

blackened significantly. On the other hand, if the methane was switched off at the end of regeneration and only nitrogen flowed over the sorbent, coke rapidly disappeared as indicated by a very rapid decrease in mass. It was also observed that under these conditions the sorbent regained its off-white color and no blackened areas remained. These observations led us to hypothesize the reaction scheme indicated by equations 34 to 36 which needs to be confirmed by the analysis of the regenerated sorbent.

Figures 38 to 40 show the mass changes during regeneration under different conditions. Comparison of figures 38 and 39 indicate that as temperature increases, the time to reach the minimum mass decreases. Since the minimum in the observed mass is the result of the mass decrease due to reaction 34 and the mass increase due to reaction 35, it can be concluded that the activation energy of the coking reaction (reaction 35) is greater than the activation energy of the regeneration reaction (reaction 34). Similarly, from reactions 35 and 36 it can be concluded that since the time to reach minimum mass increases with decreasing methane partial pressure, the order of the regeneration reaction with respect to methane is positive and is smaller than the order of the coking reaction with respect to methane. Since copper sulfate is reduced to elemental copper during regeneration, coking was not observed during the regeneration of copper oxide-based sorbents⁽¹⁸⁾.

Figure 38. Thermogram for Regeneration
with Methane on 4.39% Ce (MP) on Alumina
Particles; CH₄= 100%; T= 873K

Figure 39. Thermogram for Regeneration with Methane on 4.39% Ce (MP) on Alumina Particles; CH₄= 100%; T= 923K

Thermogram for Regeneration with Methane on 4.39% Cerium on Alumina

Figure 40. Thermogram for Regeneration with Methane on 4.39% Ce on Alumina Particles; CH₄= 15%; T= 923K

regeneration of copper oxide-based sorbents⁽¹⁸⁾.

VI.A.2.d. Effect of regeneration gas composition

Figure 41 shows the conversions for regenerations with different methane concentrations. From this figure it can be seen that the final conversion decreases as the methane concentration increases. This observation can be explained by the faster coverage of the sorbent surface with carbon at higher methane concentrations, thus, slowing down the reaction of the sorbent with methane. On the other hand, since coking is not significant at the start of regeneration, the initial rate of the regeneration reaction increases with increasing methane concentrations. The order of the initial rate of regeneration with respect to methane was found to be 0.76.

VI.A.2.d. Effect of temperature

Assuming an Arrhenius type of temperature dependence for the initial reaction rate, an activation energy of 130 kJ/mol was found for the regeneration with methane. This value is higher than that found for regeneration with hydrogen. Figure 42 shows the effect of temperature on conversion. Temperature affects conversion in two ways. It increases the rate of regeneration reaction thus tends to increase the conversion at any time, but, it also increases the rate of the coking reaction thus decreasing the available surface for regeneration. As seen in Figure 42, the first effect results in increasing conversions with

Figure 41. Effect of Gas Composition on Conversion for Rgeneration with Methane on 4.39% Ce(MP) Alumina Particles; T=923K

Figure 42. Effect of Temperature on Conversion for Regeneration with Methane on 4.39% Ce (MP) on Alumina; $\text{CH}_4 = 15\%$

temperature up to 923 K. At higher temperatures the second effect becomes dominant and conversion decreases.

VI.A.2.e. Effects of SO_2 and CO_2

Figure 43 shows the effects of CO_2 and SO_2 on the conversion for regeneration with methane. It is clearly seen that the presence of SO_2 in the regeneration gases decreases both the final conversion and the regeneration rate. The removal of SO_2 from the regeneration gases appears to restore the conversion. This observation can be explained by the competitive adsorption of SO_2 and CH_4 . Figure 44 shows a similar effect of SO_2 on regeneration with hydrogen. Another interesting observation from Figure 43 is the effect of CO_2 . It appears that the presence of CO_2 suppresses coking and thus increases the conversion.

VI.A.2.f. Effect of heating atmosphere

Figures 45 and 46 show the effect of the atmosphere under which the sorbent is heated to the regeneration temperature. The effect on regeneration with methane is not very significant (Figure 45). If the regeneration gases contain SO_2 , the conversion appears to be higher due to the fact that the adsorbed SO_2 is also removed during regeneration. Figure 46 shows that the effect of the presence of SO_2 in the heating atmosphere is quite dramatic when regeneration is done with hydrogen. The regeneration rate is significantly reduced while the conversion

Figure 43. Effect of SO₂ and CO₂ on Conversion for Regeneration with Methane on 4.39%Ce(MP)on Alumina;CH₄= 15%;T=923K

Figure 44. Effect of SO₂ on Conversion for Regeneration with Methane on 4.39% Ce (MP) on Alumina; H₂=10%; T=873 K

Figure 45. Effect of Heating Atmosphere
Before Regeneration on Conversion; 4.39%
Ce (MP) on Alumina; $\text{CH}_4=15\%$; $T=923\text{ K}$

Figure 46. Effect of Heating Atmosphere Before Regeneration on Conversion for Regeneration with Methane; $H_2=10\%$

appears to be very high due to the removal of adsorbed SO_2 similar to regeneration with methane.

VI.A.2.g.Cyclling behavior with methane regeneration

A sorbent sample was subjected to 5 sulfation-regeneration cycles with methane as the regeneration gas. Figure 47 shows that there is a significant difference between the sulfur capacities of the fresh and regenerated sorbents. This difference is higher than that observed with hydrogen as the regeneration gas. With methane the final S/Ce ratios obtained with regenerated sorbents were slightly above 1.5 (1.0 with JL analysis) while this number was slightly above 2 (around 1.4 with JL analysis) when regeneration was done with hydrogen. This may be due to different solid species being formed when regeneration was done with methane. The S/Ce ratios obtained for subsequent cycles indicate that regeneration with methane results in very stable sorbent sulfur capacity which did not change for 4 sulfation-regeneration cycles.

VI.B. Sulfation of the Sorbent

Tests 72-79 were run with sorbent particles to determine the activation energy of the sulfation reaction. The initial sulfation rate data from these tests were fitted by the linear least squares method by using equations 17 and 18. An activation energy of 19

Figure 47. Effect of Cycling on S/Ce
 T=873 K; Regen. Gas:SO₂=0.3%, CH₄=15%;
 4.39% Ce (MP) on Alumina Particles

kJ/mole was obtained. This is somewhat higher than the 12 kJ/mole value reported by Hedges and Yeh⁽²⁾.

The results of the tests with water and ammonia were not very reproducible as was observed from replicate experiments. This was hypothesized to be due to contamination in the lines due to the deposition of ammonium sulfate. The lines were opened after these experiments and appreciable white solid deposits were found in them. Therefore, some changes were made in the experimental setup with respect to the introduction of ammonia and water vapor, and these tests were repeated and the results are discussed in the following section.

Preliminary kinetic studies indicated a 12% decrease in the initial rate of sulfation upon the addition of 500 ppm ammonia.

VI.B.1. The Effect of Temperature and SO₂ Partial Pressure

The replicate runs to study the effect of temperature and SO₂ partial pressure on the rate of sulfation and to study the effect of ammonia on sulfation were performed on fresh sorbent for each run; the particle size of the sorbent was 90-150 μ m. The sample size was nominally 3 mg. These runs were repeated because there was the possibility of confounding with the cycling of the sorbent in the data presented in the previous section.

For these runs a sorbent after the following treatment was used: A large amount of ALCOA16-CE4-VI sorbent was placed in a quartz reactor and sulfated under 200 cc/min of standard

sulfation gas (SO_2 : 3000 ppm, O_2 : 3 %, CO_2 : 14 %, and N_2 : 82.7 %) at 873 K. Subsequently, the sorbent was regenerated with hydrogen for three hours and then oxidized with 6.6 % oxygen in nitrogen. This pretreatment generated a sorbent characteristic of the sorbent in the second cycle. This approach was adopted because the sorbents showed very reproducible behavior after the first cycle.

The data from the repeated runs to study the effect of temperature and SO_2 partial pressure on the rate of sulfation were evaluated by calculation of the initial rate, and the S/Ce ratios as a function of time and conversion during sulfation. As was done previously, reaction (6) was assumed to take place during sulfation. Equations (11) and (12) are again used to calculate S/Ce and X_s . Equations (16) and (18) were fitted to the initial rate data to estimate the order of the sulfation reaction with respect to SO_2 and the activation energy of the sulfation reaction.

Figures 48 - 50 show the sulfur capacity of the sorbent as a function of temperature and partial pressure of SO_2 , respectively. The sorbent capacity is reported as S/Ce ratio calculated using the Malcolm Pirnie analyses. For results based on the analysis of Jennings Laboratories these S/Ce ratios need to be multiplied by 0.67. The figures indicate that the sulfur capacity of the sorbent increases with both temperature and SO_2 partial pressure. S/Ce ratio is comparable with those obtained on

Figure 48. Effect of Temperature on S/Ce
 SO₂-3000 ppm; cycle 2; 4.39% Ce (MP) on
 90-150 micron ALCOA Alumina Particles

Figure 49. Effect of SO₂ Concentration on S/Ce; T-873 K; 4.39% Ce (MP) on 90-150 micron ALCOA Alumina Particles

Figure 50. Effect of SO₂ Concentration on S/Ce; T=773 K; 4.39% Ce(MP) on 90-150 ALCOA Alumina Particles

the fresh sorbent, which was about 2.5 at 873 K (based on Malcolm Pirnie analysis). Table 4 summarizes the effects of temperature and sulfur dioxide partial pressure on sorbent sulfur loading after 50 minutes of sulfation.

Table 4. Effect of Temperature and p_{SO_2} on S/Ce at 50 minutes
Sorbent: ALCOA 16-CE4-VI; second cycle (MP: Malcolm Pirnie, JL: Jennings Laboratory).

Temperature, K	C_{SO_2} , ppm	S/Ce		R_{SO} , mol/g.s $\times 10^{-6}$
		MP	JL	
873	3000	2.257	1.512	2.434
773	3000	1.659	1.112	1.909
823	3000	2.053	1.376	2.529
673	3000	1.261	0.845	1.305
873	1500	1.973	1.322	1.118
873	2000	2.093	1.402	1.369
873	5000	2.417	1.620	5.277
773	5000	1.658	1.111	2.743
773	2000	1.460	0.978	1.504
773	1500	1.632	1.093	0.951

This table can be compared with Table 3 to observe the difference in the sulfur capacity of the sorbent in the first and second cycles and the confounding effect of cycling on the previous data; but the results appear to be reproducible.

The dependence of the sulfation rate on these variables have also been calculated from initial rate data by using equations 16 and 18. The following results were obtained from the fitting

of the data to these equations by the linear least squares method:

$$E = 17 \text{ kJ/mol}$$

$$m = 1.33 \quad \text{at } 873 \text{ K}$$

$$m = 0.82 \quad \text{at } 773$$

VI.B.2. Effect of Ammonia on Sulfation

The data from the repeated runs to study the effect of ammonia on the rate of sulfation and sorbent capacity were evaluated by calculation of the initial rate, and the S/Ce ratios as a function of time and conversion during sulfation using the procedure outlined in the previous section.

Figures 51 - 57 show the effect of ammonia on the sulfur capacity of the sorbent (as S/Ce ratio) at different temperatures and for different SO_2 partial pressures. Table 5 shows the effect of ammonia on the initial rate of sulfation and sorbent capacity (as S/Ce ratio) after 50 minutes of sulfation.

For the data in Table 5, two facts should be noted: The S/Ce values at 50 minutes does not represent the ultimate sorbent capacity under the conditions specified, but is an indication of the overall sulfation rate. This argument is based on the observation from Figures 50 - 57 that beyond 50 minutes, S/Ce ratios increase at almost constant rate indicating that the sorbent might end up capturing about 2.5 S atoms per Ce atom (1.7 for JL analysis) if sufficient sulfation time is allowed.

Figure 61. Effect of Ammonia on S/Ce
 SO₂-3000 ppm; T=873 K; 4.39% Ce (MP) on
 90-150 micron ALCOA Alumina Particles

Figure 52. Effect of Ammonia on S/Ce
 SO_2 -3000 ppm; $T=773 \text{ K}$; 4.39% Ce (MP) on
 90-150 micron ALCOA Alumina Particles

Figure 53. Effect of Ammonia on S/Ce
 SO₂=3000 ppm; 4.39% Ce (MP) on 90-150
 micron ALCOA Alumina Particles

Figure 64. Effect of Ammonia on S/Ce
 SO₂=1500 ppm; T=873 K; 4.39% Ce (MP) on
 90-150 micron ALCOA Alumina Particles

Figure 55. Effect of Ammonia on S/Ce
 T=873 K; SO2=5000 ppm; 4.39% Ce (MP) on
 90-150 micron ALCOA Alumina Particles

Figure 56. Effect of SO₂ Concentration on S/Ce. T=873 K; no ammonia; 4.39% Ce (MP) on 90-150 micron Alumina Particles

Figure 57. Effect of SO₂ Concentration on S/Ce. T=873 K; NH₃=500 ppm; 4.39% Ce (MP) on 90-150 micron Alumina Particles

Table 5. Effect of Ammonia on the Initial Sulfation Rate (R_{SO}) and on S/Ce at 50 minutes for Different Temperatures and p_{SO_2} .

Sorbent: ALCOA 16-CE4-VI; second cycle (MP: Malcolm Pirnie, JL: Jennings Laboratories)

C_{NH_3} , ppm	Temperature, K	C_{SO_2} , ppm	S/Ce		R_{SO} , mol/g.s x 10^{-6}
			MP	JL	
0	873	1500	1.973	1.322	1.1185
250	873	1500	1.875	1.163	1.1393
350	873	1500	2.066	1.384	0.89343
500	873	1500	1.476	0.989	0.93546
0	873	3000	2.257	1.512	2.4342
250	873	3000	2.009	1.346	2.5009
350	873	3000	2.174	1.457	2.2883
500	873	3000	1.636	1.109	1.6713
0	873	5000	2.417	1.619	5.2772
250	873	5000	2.275	1.524	4.3314
350	873	5000	1.995	1.337	2.7660
$\frac{1}{T}$ 500	873	5000	1.003	0.672	3.8794
0	773	3000	1.659	1.111	1.9094
250	773	3000	1.264	0.847	1.0147
350	773	3000	1.728	1.157	2.0587
500	773	3000	1.615	1.082	1.5646

Secondly, the comparison of the overall rate indicated by the S/Ce ratio at 50 minutes and the initial rates given in the last column should indicate whether the observed effect of ammonia is on the sulfation kinetics or due to changes in surface area or in the magnitudes of mass transfer resistances.

With the above considerations the following observations can be made:

- The effect of ammonia appears to be minimum for 350 ppm ammonia (250 ppm with 5000 ppm SO_2) at both 873 and 773 K. Introduction of 500 ppm ammonia results in a significant decrease in the overall rate at 873 K but this effect is smaller at 773 K.
- Same observations can be made for initial rates at 773 K but at 873 K no definite trend can be observed for the effect of ammonia on the initial rate.

The observations on the effect of ammonia on sorbent capacity may be misleading because the S/Ce ratios were determined by assuming all the weight gain during sulfation to be the result of Equation 6. It is possible that some of the weight gain is the result of the formation of ammonium sulfate species on the surface as discussed below.

Several processes may take place when sulfation gases contain some ammonia. Since it has been reported that⁽²²⁾ ceria - based sorbents have high activity and selectivity for catalytic reduction of NO with ammonia at high temperatures (above 773 K), it is expected that some ammonia will chemisorb on the sorbent forming ammonium sulfate species. At the high temperatures under consideration these species are unstable and will decompose giving SO_3 and H_2O , or the sulfates may be reduced by ammonia on the surface to sulfites which may desorb forming SO_2 and H_2O . Ammonia may also be oxidized to N_2 and H_2O or may form some nitrate species on the surface which may further react with

ammonia to form nitrogen oxides. The rate of chemisorption of ammonia will depend on the temperature and partial pressure of ammonia. The rates of decomposition of surface species and desorption also depend on temperature. Without any further information about the surface species, adsorption and desorption rates, and reactor effluent compositions, only a tentative explanation of our observations can be proposed.

The apparent increase in the S/Ce ratios, which we will assume to be due to the chemisorption of ammonia and formation of surface ammonium sulfate species, will increase with ammonia partial pressure and decrease with temperature. Rate of decomposition of surface species will increase with the concentration of surface ammonium sulfates and with temperature. Also, larger ammonia partial pressures may enhance reduction of surface sulfates and facilitate the decomposition of surface species. In summary, the increase in the ammonium sulfate species on the surface will increase the apparent S/Ce ratio and the decomposition of these species will result in sulfur loss and decrease the S/Ce ratio. From the observed S/Ce ratios, it appears that at low ammonia partial pressures, the rate of formation of surface ammonia species is faster than their decomposition and hence apparent S/Ce ratios are larger. On the other hand, at higher ammonia partial pressures the decomposition and reduction of surface sulfates become significant and lower S/Ce ratios are observed.

Observations with 5000 ppm SO_2 indicate that at high SO_2 partial pressures, even a small amount of ammonia causes sulfur loss from the surface and there is no apparent increase in the S/Ce ratio with ammonia addition.

VI.B.2.a. The Effect of Ammonia on Sulfation in the Presence of Water Vapor

Figure 58 shows the effect of ammonia in the presence of 4% water vapor. It is apparent that the presence of water vapor modifies the various mechanisms discussed in the previous section and increases the sulfur loss from the surface of the sorbent. This effect increases with increasing ammonia partial pressures.

VI.C. The Effect of Cerium Content on the Sorbent Performance

To observe the effect of cerium content the following sorbents were used:

- ALCOA-CE4-IV, cerium loading 1.59% by mass (3.2% JL)
- ALCOA-CE4-VI, cerium loading 4.39% by mass (6.6% JL)
- ALCOA-CE8-II, cerium loading 7.64% by mass (15.8% JL)
- ALCOA-CE12-I, cerium loading 9.28% by mass (20.1% JL)

The ALCOA16-CE4-VI sorbent has been investigated, and the results have been reported before. The other sorbents were subjected to four cycles of successive sulfation, regeneration, and oxidation. Sulfation was performed under 200 cc/min of standard sulfation gas (SO_2 : 3000 ppm, O_2 : 3 %, CO_2 : 14 %, and N_2 : 82.7 %) at 873 K. Subsequently, the sorbent was regenerated with

Figure 58. Effect of Ammonia in Wet Gas on Sorbent Performance. $H_2O=4\%$; Standard Conditions; 4.39%Ce(MP) 90-150m Particles

hydrogen and then oxidized with 6.6 % oxygen in nitrogen .

The cyclic behaviors of the sorbents containing 1.59% (3.2 by JL), 7.64% (15.8 by JL), and 9.28% (20.1 by JL) cerium by mass are shown in figures 59, 60, and 61, respectively. The extremely high S/Ce ratios for the 1.59% Ce containing sorbent was attributed to an error in the determination of the cerium content of the sorbent, which is expected due to the very low metal concentration. Although the S/Ce ratios for the other sorbents are within the reasonable range we have decided to repeat the metal analyses. As reported earlier, analyses by Jennings Laboratories gave cerium mass fractions that are about a factor of two larger than those reported by Malcolm Pirnie. Jennings Laboratories results showed that the cerium loadings were possibly much larger than the intended loadings and some exceeded monolayer coverage.

Figures 59, 60, and 61 show that all the sorbents show a very stable performance after the first cycle and show an improvement in the sulfur capture capacity after the third cycle.

Figure 62 shows the comparison of the second cycles of all the sorbents tested based on Malcolm Pirnie analysis and Figure 63 presents the same using Jennings Laboratory analyses. If the MP results were used, disregarding the 1.59% Ce sorbent for the apparent error, it appears that increasing the cerium content of the sorbent decreases the S/Ce ratio probably due to the decrease in the surrounding surface alumina sites as monolayer coverage is

Figure 59. Sulfation-Regeneration Cycles for 1.59% Ce (MP) on 90-150 m Alumina Particles. Standard Conditions.

Figure 60. Sulfation-Regeneration Cycles for 7.64% Ce (MP) on 90-150 m Alumina Particles. Standard Conditions

Figure 61. Sulfation-Regeneration Cycles for 9.28% Ce (MP) on 90-150 micron Alumina Particles. Standard Conditions.

Figure 62. Effect of Cerium Content on Sorbent Performance. MP Analysis; Standard Conditions.

approached. These surrounding alumina sites are needed for the formation of aluminum sulfate species and thus regeneration of ceria sites for further sulfur removal. If the JL results are used, more reasonable results are obtained: Figure 63 shows that for cerium loading of 3.2% since alumina to ceria ratio is large, the amount of surface aluminum sulfate species formation is significant and the S/Ce atom ratio approaches 2.5. For 6.55% cerium loading the contribution of alumina to sulfation is much smaller indicated by final S/Ce ratios only slightly above 1.5. Both the 15.8 and 20.1% cerium loadings produce coverages above the monolayer coverage. For these the inaccessibility of alumina and the first ceria layer results in much lower S/Ce ratios which approach one at very long times.

From these results it is apparent that the cerium loading on the sorbent should be less than the monolayer coverage of the support. For less than monolayer coverage, the optimum cerium loading will be determined by the trade off between the higher cerium efficiency at lower loadings and larger sorbent mass needed.

VI.C.1. Effect of Cerium Content on the Order of Reaction With Respect to the Solid Reactant

It has been observed that with the sorbent containing 4.39% (6.55% with JL results) cerium by mass the sulfation reaction was first order with respect to cerium oxide only up to about 40%

Figure 63. Effect of Cerium Content on Sorbent Performance. JL Analysis; Standard Conditions.

conversion. The new data obtained for sorbents containing 7.64% (15.8% JL) and 9.28% (20.1% with JL) cerium indicated that with these sorbents, the dependence of reaction rate on cerium oxide is first order up to about 90% conversion (Figure 64). Since the monolayer coverage corresponds to about 10% for the alumina used as support, it appears that as monolayer coverage is approached (exceeded with JL results) the rate of sulfation is controlled by kinetics only

VI.D. The Effect of Flyash on Sulfation

The flyash to sorbent mass ratios used in these runs are much higher than those that will be encountered by the sorbent in the commercial units. The reason for this is the difficulty and inaccuracy of measuring very small amounts of fly ash. Fly ash was obtained from Malcolm Pirnie and visual observation suggested significant carbon content.

Figures 65, 66 and 67 show the thermograms obtained for sulfation in the presence of flyash. The thermograms in figures 65 and 66 show that after a short period of rapid mass increase due to sulfate formation, the mass starts to decrease slowly, passes through a minimum and starts increasing again at a rate typical of sulfation without the fly ash. This observation indicates the presence of different mass-decreasing reactions due to the carbon in the fly ash. Initially the rate of sulfation of the metal is very fast and the sorbent mass

Figure 64. First Order Dependence on Solid Reactant. Standard Conditions; 9.28% Ce (MP) on Alumina Particles.

DATE: 05-31-96
FILE: SMOOTHED
ASH600-2.DAT

HIGHASH-T600

THERMO-GRAVIMETRIC
ANALYSIS

Figure 65. Thermogram with flyash/sorbent
= 0.482. Standard Conditions;
4.39% Ce (MP) on Alumina Particles

DATE: 05-01-95
 FILE: SMOOTHED
 ASH500NH.DAT

CAHN

THERMO-GRAVIMETRIC
 ANALYSIS

Figure 66. Thermogram with flyash/sorbent
 =0.413. 500 ppm ammonia. Standard
 Conditions. 4.39% Ce(MP).

DATE 08-24-86
FILE SMOOTHED
ASH600.DAT

FLYASH-600

THERMOGRAVIMETRIC
ANALYSIS

Figure 67. Thermogram with Flyash/sorbent
=0.158. Standard Conditions;
4.39% Ce (MP) on Alumina Particles

increases. As the sulfation rate gets slower, the reactions of carbon with gaseous SO_2 , surface SO_3 , and solid sulfate becomes significant and the mass decreases as the result of loss of carbon and sulfur. Eventually, as the carbon is depleted, mass loss decreases and mass increases due to sulfation which again becomes the dominant process.

The sorbent mass used in Figure 67 is smaller and the effect of the flyash is not readily observed from this chromatogram.

The results for the effect of flyash are summarized in Table 6. The initial rate of sulfation appears to be slightly improved by the presence of flyash but the amount of flyash does not seem to affect the sulfation rate in the range of flyash/sorbent ratios tested. From figures 65, 66 and table 6 no significant effect of ammonia was observed in the presence of flyash.

Table 6. The Effect of Flyash on the Initial Sulfation Rate

Flyash/sorbent mass ratio	Ammonia conc. (ppm)	Initial rate (mmol sulfate/s)
0.0	0.0	2.43e-06
0.158	0.0	3.23e-06
0.482	0.0	3.25e-06
0.413	500	3.23e-06

VII. EVALUATION OF THE COMMERCIAL SCALE CERIA PROCESS

Our negotiations with Malcolm Pirnie, Inc. has indicated that the resources allocated by Malcolm Pirnie to this task were

not adequate for the successful completion of the task. Therefore we have contacted TECOGEN of Waltham, MA, and asked them if they could modify the software they have developed for the evaluation of the copper oxide sorbent, to accommodate the ceria sorbent. Upon their acceptance we have sent a task order containing the data we have obtained on ceria sorbents (Appendix I). The sulfation rate indicated on the task order was based on initial rate data and was found to be inadequate at longer times. The following updated rate equation was obtained by fitting all the reaction data to a first order reaction equation:

$$\frac{dX_s}{dt} = 1.94 \exp\left(-\frac{2045}{T}\right) y_{SO_2} (1 - X_s) \quad (34)$$

where X_s is the fractional conversion of cerium oxide, y_{SO_2} is the mole fraction of SO_2 , T is the temperature in K, and t is the time in seconds. This equation holds up to 94% conversion. The correlation coefficient for the linear fit of $\ln(1-X_s)$ versus time data is 0.99788 and the standard error of estimate is 0.0614.

The rate of regeneration with hydrogen was found to be affected significantly by SO_2 partial pressure. Therefore the initial reaction rates, when only insignificant amounts of SO_2 are present, cannot be used for the design purposes. A new rate equation for regeneration with hydrogen which takes into account the inhibition by SO_2 was found by obtaining the activation energy and the pre-exponential factor from the initial rate data

and subsequently using a Langmuir-Hinshelwood type expression for dissociative adsorption of hydrogen and co-adsorption of SO₂.

$$r_H = 5400 c_0 e^{\frac{-13700}{T}} (1 - x_H) \frac{y_{H_2}}{[1 + (23y_{H_2})^{1/2} + 170y_{SO_2}]^2} \quad (35)$$

where

r_H = moles Ce₂(SO₄)₃ reacted per second per mg of fresh sorbent,

c_0 = mass fraction of cerium in fresh sorbent,

x_H = fractional conversion of Ce₂(SO₄)₃,

y_{H_2} = mole fraction of hydrogen in regeneration reactor, and

y_{SO_2} = mole fraction of SO₂ in regeneration reactor.

This equation holds up to 96% conversion above which the rate is probably mass transport controlled.

For regeneration with methane the rate equation

$$r_M = 346 e^{\frac{-15600}{T}} y_M^{0.76} c_0 (1 - x_M) \quad (36)$$

where the subscript M indicates methane, was found to adequately represent the regeneration rate with methane.

The details of the preliminary design and economic analysis of the ceria process and comparison with the copper oxide process is given in the TECOGEN report included in Appendix 1. Their results indicate that the copper oxide process has a lower overall cost of SO₂ removal mainly because the operating temperature allows the use of carbon steel equipment while the ceria process operates where stainless steel have to be used. For methane regeneration the ceria process has higher operating and

maintenance costs due to the larger circulation rate, and therefore attrition rate, of the sorbent. In the analysis the ceria sorbent was assumed to have the same attrition resistance as the CuO sorbent. Therefore, if the attrition resistance of the ceria sorbent is higher (ceria is known to increase the hydrothermal stability of alumina in automobile exhaust catalysts) the operating and maintenance costs for the ceria process may decrease to levels even below those of the copper oxide process. For regeneration with hydrogen, higher cost of sorbent circulation is offset by the lower regeneration gas flow.

VIII. BIBLIOGRAPHY

1. Yeh, J. T., Demski, R. J., Strakey, J. P., and Joubert, J. I. "Combined SO₂/NO_x Removal from Flue Gas", *Environmental Progress*, 4(4), pp.223-228 (1985).
2. Yeh, J. T., Drummond, C. J., Joubert, J. I., "Process Simulation of the Fluidized-Bed Copper Oxide Process Sulfation Reaction", *Environmental Progress*, 6(1), pp. 44-50 (1987).
3. Hedges, S. W. and R. A. Diffenbach, "Thermogravimetric study of Novel Sorbents for Flue Gas Cleanup", Proceedings of the 25th Intersociety Energy Conversion Engineering Conference, vol. 6, pp.185-190 (1990).
4. Hedges, S. W. and J. T. Yeh, "Kinetics of Sulfur Dioxide Uptake on Supported Cerium Oxide Sorbents", *Environmental Progress*, in press (1992).
5. Friedman, R. M., J. J. Freeman, and F. W. Lytle, "Characterization of Cu/Al₂O₃ Catalysts", *Journal of Catalysis*, 55, pp. 10-28 (1978).
6. Strohmeier, B. R., Leyden, D. E., Field, R. S., Hercules, D., "Surface Spectroscopic Characterization of Cu/Al₂O₃ Catalysts", *J. Catal.* 94514-530 (1985).
7. Pollack, S. S., W. P. Chisholm, R. T. Obermyer, S. W. Hedges, M. Ramanathan, and P. A. Montano, "Properties of Copper/Alumina Sorbents Used for the Removal of Sulfur Dioxide", *Ind. Eng. Chem. Res.*, 27, pp. 2276-2282 (1988).
8. Centi, G., A. Riva, N. Passarini, G. Brambilla, B. K. Hodnett, B. Delmon, and M. Ruwet, "Simultaneous Removal of SO₂/NO_x From Flue Gases. Sorbent/Catalyst Design and Performances", *Chem. Eng. Sci.*, 45(8), pp. 2679-2686 (1990).
9. Harriott, P. and J. M. Markussen, "Kinetics of Sorbent Regeneration in the Copper Oxide Process for Flue Gas Cleanup", *Ind. Eng. Chem. Res.*, 31, pp. 373-379 (1992).
10. McCrea, D. H., A. J. Forney, and J. G. Myers, "Recovery of Sulfur from Flue Gases Using a Copper Oxide Absorbent", *Journal of the Air Pollution Control Association*, 20(12), pp. 819-824 (1970).
11. Strakey, J. P., E. R. Bauer, Jr., and W. P. Haynes, "Removal

of SO_2 and NO_x from Flue Gas in Fluidized-Bed Copper Oxide Process", presented at the 6th National Conference on Energy and Environment, Pittsburgh, PA, May 21-24, 1979.

12. Williamson, R. R., J. A. Movici, and T. L. LaCross, "Sorbent Life-Cycle Testing Fluidized-Bed Copper Oxide Process", project report for the Department of Energy, UOP, Des Plaines, IL, 1988.
13. Shyu, J. Z., W. H. Weber, and H. S. Gandhi, "Surface Characterization of Alumina-Supported Ceria", *J. Phys. Chem.*, **92**, pp. 4964-4970 (1988).
14. Doraiswami, L. K. and B. D. Kulkarni, "Gas-Solid Noncatalytic Reactions", in *Chemical Reaction and Reactor Engineering*, J. J. Carberry and A. Varma, eds, p.293, Marcel Dekker, New York (1987).
15. Hartman, M., J. Hejna, and Z. Beran, "Application of the Reaction Kinetics and Dispersion Model to Gas-Solid Reactors for Removal of SO_2 from Flue Gas", *Chem. Eng. Sci.*, **34**, p. 475 (1979).
16. Evans, J. W. and S. Song, "Application of Porous Pellet Model to Fixed, Moving and Fluidized Bed Gas-Solid Reactors", *Ind. Eng. Chem. Process Des. Dev.*, **13**, p. 146 (1974).
17. Larsen, E. S. and M. Pilat, "Design and Testing of a Moving Bed VOC Adsorption System", *Environmental Progress*, **10**(1), pp. 75-82 (1991).
18. Markussen, J. M., Pennline, H. W., and Brodd, C. F., "A Microbalance Study of the Sorbent Regeneration Kinetics in the Copper Oxide Process", presented at the AIChE 1994 Summer National Meeting, Denver, CO, August 14-17, 1994.
19. Centi, G., A. Riva, N. Passarini, S. Perathoner, and A. Riva, "Combined $\text{DeSO}_x/\text{DeNO}_x$ Reactions on a Copper on Alumina Sorbent-Catalyst. 1. Mechanism of SO_2 Oxidation-Adsorption", *Ind. Eng. Chem. Res.*, **31**, pp. 1947-1955 (1992).
20. Centi, G., A. Riva, N. Passarini, S. Perathoner, and A. Riva, "Combined $\text{DeSO}_x/\text{DeNO}_x$ Reactions on a Copper on Alumina Sorbent-Catalyst. 2. Kinetics of the DeSO_x Reaction", *Ind. Eng. Chem. Res.*, **31**, pp. 1956-1963 (1992).
21. Levenspiel, O., *Chemical Reaction Engineering*, Second ed., John Wiley & Sons, New York, 1972.

22. Longo, T. M. and Cull, N. L., "Process for the Removal of SO_2 and NO_x from Gaseous Mixtures Containing the Same," U. S. Patent #4251496, 1981.

APPENDIX A

Task Order to TECOGEN

HAMPTON UNIVERSITY
Department of Chemical Engineering
Hampton, VA 23668

Telephone: (804) 727-5599

Fax: (804) 727-5189

e-mail: ates@et.hamptonu.edu

TASKS TO BE PERFORMED BY THE CONSULTANT

The process to be evaluated will be very similar to the COBRA copper oxide process, but it will use a different metal oxide as the sorbent and the sulfation and regeneration reactors will operate at temperatures between 773 K and 873 K. The specific tasks to be performed under this purchase order are stated below. The time available for the completion of these tasks is 5 weeks from the receipt of the purchase order. The information on the specific sorbent to be used is supplied on the attached sheets.

Task 1: Model a cross-flow moving-bed sulfation reactor for the metal oxide sorbent to be specified. For two reactor operating temperatures (823 K, 873 K), and two sorbent sizes (1/16 in, 1/8 in), the following information is needed from the model:

- ▶ Size and cost of the reactor.
- ▶ Sorbent needed to process a specified gas flow rate.
- ▶ Gas exit temperature for adiabatic operation.

Task 2: Model a cross-flow moving-bed regeneration reactor for the metal oxide sorbent to be specified. For the two regenerator operating temperatures specified on the attached sheet, two sorbent sizes (1/16", 1/8"), and two different regeneration gases (methane and hydrogen), the following information is needed from the model:

- ▶ Size and cost of the regenerator.
- ▶ Gas exit temperature for adiabatic operation.

Task 3: Compare the cost of the process with that of the process using copper oxide sorbent. In the cost comparison the following effects should be considered:

- ▶ Effects of the different sulfation and regeneration kinetics on the reactor and regenerator costs.
- ▶ Effect of higher operating temperatures on the reactor and regenerator costs.
- ▶ Effect of different heats of reactions on the total cost (energy credit from exothermicity). Thermodynamic data for solid species will be supplied if needed.
- ▶ Effect of sorbent cost on total cost for three specified cost ratios (ratio of the cost of ceria sorbent to the cost of copper oxide sorbent equal to 1, 1.2, and 1.4).

TECHNICAL INFORMATION

Sorbent: 9% by mass cerium (as CeO_2) on alumina (1/16-in and 1/8-in spheres).

Reactions: Sulfation

$$r_s = 0.205 \exp\left[-\frac{2050}{T}\right] y_{\text{SO}_2} c_0 (1 - X_s)$$

Regeneration with hydrogen

$$r_H = 2420 \exp\left[-\frac{13700}{T}\right] y_H^{0.56} c_0 (1 - X_H)$$

Regeneration with Methane

$$r_M = -346 \exp\left[-\frac{15600}{T}\right] y_M^{0.76} c_0 (1 - X_M)$$

Very fast oxydation (assumed instantaneous) on contact with sulfation gases

In the rate equations r_s is the sulfation rate in moles of Ce_2O reacted per second per gram of sorbent; r_H and r_M are the regeneration rates with hydrogen and methane, respectively in moles of sulfate reacted per second per gram of sorbent; T is the reaction temperature in K; y_s , y_H , and y_M are the mole fractions of SO_2 , H_2 , and CH_4 , respectively; c_0 is the mass fraction of Ce on the sorbent (as prepared); X_s is the fractional conversion of CeO_2 ; and X_H and X_M are the fractional conversion of the sulfate.

Gas Composition: Default with 3000 ppm SO_2

Gas temperature: For sulfation 823 K and 873 K; for regeneration with hydrogen 823 K

TECHNICAL INFORMATION

Sorbent: 9% by mass cerium (as CeO_2) on alumina (1/16-in and 1/8-in spheres).

Reactions: Sulfation

$$r_s = 0.205 \exp\left[-\frac{2050}{T}\right] y_{\text{SO}_2} c_0 (1 - X_s)$$

Regeneration with hydrogen

$$r_H = 2420 \exp\left[-\frac{13700}{T}\right] y_H^{0.56} c_0 (1 - X_H)$$

Regeneration with Methane

$$r_M = -346 \exp\left[-\frac{15600}{T}\right] y_M^{0.76} c_0 (1 - X_M)$$

Very fast oxydation (assumed instantaneous) on contact with sulfation gases

In the rate equations r_s is the sulfation rate in moles of Ce_2O reacted per second per gram of sorbent; r_H and r_M are the regeneration rates with hydrogen and methane, respectively in moles of sulfate reacted per second per gram of sorbent; T is the reaction temperature in K; y_s , y_H , and y_M are the mole fractions of SO_2 , H_2 , and CH_4 , respectively; c_0 is the mass fraction of Ce on the sorbent (as prepared); X_s is the fractional conversion of CeO_2 ; and X_H and X_M are the fractional conversion of the sulfate.

Gas Composition: Default with 3000 ppm SO_2

Gas temperature: For sulfation 823 K and 873 K; for regeneration with hydrogen 823 K

and 873 K; for regeneration with methane 873 K and 923 K.

Gas Pressure: Default

Sorbent Size: 1/16" and 1/8"

Maximum Sulfur Capture: 2 sulfur atoms per cerium atom

Maximum Pressure Drop: Default

Maximum Outlet SO₂: Default

Heats of Reaction: Standard heat of reaction for the sulfation of CeO₂:

$$\Delta H_s(298 \text{ K}) = -294.14 \text{ kJ/mol SO}_2$$

Standard heat of reaction for the oxidation of Ce₂O₃

$$\Delta H_o(298 \text{ K}) = -119.46 \text{ kJ/mol SO}_2$$

$$\text{Total heat of reaction for the sulfation step} = \Delta H_s + \Delta H_o$$

Standard heat of reaction for regeneration with hydrogen:

$$\Delta H_h(298 \text{ K}) = 91.16 \text{ kJ/mol SO}_2$$

Standard heat of reaction for regeneration with methane:

$$\Delta H_m(298 \text{ K}) = 258.91 \text{ kJ/mol SO}_2$$

APPENDIX B

TECOGEN Report

**Sulfur Dioxide Adsorption on Metal
Oxides Supported on Alumina**

Prepared for:
Hampton University
Department of Chemical Engineering
Hampton, VA 23668

Prepared by:
Dr. Matthew R. Hyre
Tecogen
A Division of Thermo Power Corporation
A Thermo Electron Company
45 First Avenue
P.O. Box 8995
Waltham, MA 02254-8995

Sulfur Dioxide Adsorption/Regeneration on Metal Oxides Supported on Alumina

1.0 BACKGROUND	3
2.0 INVESTIGATIONS OF THE ME-O/ Al_2O_3 CATALYST	4
2.1 $\text{CuO}/\text{Al}_2\text{O}_3$ Catalysts	4
2.2 $\text{CeO}_2/\text{Al}_2\text{O}_3$ Catalysts	4
3.0 MECHANISM OF SO_2 SORPTION	5
3.1 SO_2 Sorption on Alumina Supported CuO	5
3.2 SO_2 Sorption on Alumina Supported CeO_2	6
3.3 Postulated SO_2 Adsorption Path	6
4.0 PREVIOUS EXPERIMENTAL STUDIES OF SULFATION KINETICS	8
4.1 Unsupported Metal Oxides	8
4.2 Supported Metal Oxides	10
5.0 SUMMARY	15
6.0 ADSORPTION KINETICS	15
7.0 GOVERNING EQUATIONS	17
8.0 MODELING LARGE BATCH OR MOVING BED REACTORS	20
9.0 PRESSURE DROP DETERMINATION	20
10.0 MODEL INPUT ASSUMPTIONS	21
11.0 SULFATION MODEL RESULTS - REQUIRED NUMBER OF ADSORBER MODULES	23
12.0 REGENERATION MODELING OF Me-SO_4	25
12.1 Me-SO_4 Regeneration Studies	25
12.2 Effect of SO_2 Concentration on Regeneration Kinetics	26
12.3 Hydrogen Consumption During Regeneration	27
12.4 Catalytic Oxidation of Methane	28
13.0 MODELING LARGE COUNTERFLOW MOVING BED REGENERATORS	29
14.0 REGENERATOR MODEL INPUT ASSUMPTIONS	31
15.0 REGENERATION MODEL RESULTS - REQUIRED NUMBER OF REGENERATOR MODULES	32
16.0 COST RESULTS	36
17.0 REFERENCES	43
APPENDIX A SIMILARITIES IN BREAKTHROUGH EXPRESSIONS - ADSORPTION VS. ABSORPTION MODELING	48
APPENDIX B: ADSORBER MODEL OUTPUT	51
APPENDIX C: REGENERATOR MODEL OUTPUT	52

Sulfur Dioxide Adsorption/Regeneration on Metal Oxides Supported on Alumina

The combined SO_2/NO_x removal in a single unit operation using a supported metal oxide sorbent-catalyst offers the potential for reducing the cost of environmental control (Centi *et al.*, 1990; Drummond *et al.*, 1985; Kiel *et al.*, 1989; Yeh *et al.*, 1984, 1985, 1987). SO_2 reacts with a metal oxide (MeO) in the presence of O_2 forming a sulfate species which, in turn, catalyzes the reduction of NO to N_2 in the presence of ammonia and O_2 . The sulfate species can then be regenerated with a reducing gas such as hydrogen, methane, or synthesis gas to produce a concentrated stream of SO_2 and reduced metal (Me), which in contact with O_2 quickly transforms to the initial MeO. The economic evaluation of this technology in comparison with separate conventional flue gas desulfurization (FGD) and selective catalytic reduction (SCR) gas cleanup and with an integrated approach of combined removal of SO_2/NO_x according to some of the technologies under development (NOXSO, electron beam, activated carbon, WSA-SNOX processes) has shown the cost advantage of the integrated technologies, and in particular of that based on CuO and CeO_2 sorbents (Rubin *et al.*, 1989).

More detailed investigation of the nature, process and mechanism of interaction of the sorbent-catalyst with SO_2 and NH_3/NO_x is needed to optimize the process configuration and economics (Centi *et al.*, 1990; Kartheuser *et al.*, 1991; McCrea *et al.*, 1970; Pollack *et al.*, 1988; Waqif *et al.*, 1991).

The aim of the research reported herein was to model the kinetic behavior of a cross-flow adsorber and a counterflow regenerator using copper oxide or cerium oxide as a sorbent at various adsorption and regeneration temperatures. The modeling results were then used to approximate the levelized cost of a regenerable FGD system for both sorbents to allow for a direct economic comparison.

1.0 Background

The chemistry, mechanisms, and kinetics of the reactions of SO_2 and oxygen on metal oxides can be studied from several points of view. The approaches taken most often rely on the theories of adsorption (i.e., chemisorption), gas-solid non-catalytic and gas-solid catalytic reactions. The dividing line among these phenomena is very hard to establish, and the reaction between SO_2 and oxygen on a particular metal oxide may fall into any of the above three categories depending on the temperature, pressure and chemical composition of the system.

2.0 Investigations of the Me-O/Al₂O₃ Catalyst

2.1 CuO/Al₂O₃ Catalysts

In an early study of CuO/Al₂O₃ catalysts, Friedman *et al.* (1978) focused their attention on characterization of the system. They found that for a sample with low metal loading and treated at low calcination temperature, the copper atoms are present in the system in a distorted octahedral geometry. This is different from the copper atoms in bulk CuAl₂O₄ or bulk CuO. The copper atoms in bulk CuAl₂O₄, which is stable at high temperature, exist in a partially inverted spinel structure, in which copper atoms occupy 60 percent of tetrahedral sites and 40 percent of octahedral sites. Only for samples with high metal loading and treated at high calcination temperature was the crystal form of CuAl₂O₄ observed. No bulk CuO or CuAl₂O₄ was observed for low copper loading. This study is in agreement with that of Lo Jacono and Schiavello (1976) who observed no crystalline CuO or CuAl₂O₄ for copper loadings up to 10 percent. It also confirms the study of Selwood and Dallas (1948) who showed that the magnetic susceptibility of supported CuO is about twenty times that of unsupported CuO for copper loadings less than 11 percent, a result later attributed to effects of the aluminate surface phase (Wolberg and Roth, 1969).

Strohmeier *et al.* (1985) later studied the copper species formed on the carrier as a function of metal loading and calcination temperature. They confirmed the main conclusions of Friedman's group. Pollack *et al.* (1988) studied properties of CuO/Al₂O₃ adsorbent for SO₂. They found that for an adsorbent sample of 7.2 percent metal loading and calcined at 900 °F, the copper species are neither in the form of crystalline CuO nor CuAl₂O₄, but in a less well-defined form. The copper atoms were found to be located at a tetragonally distorted octahedral position. X-ray diffraction of a fresh sorbent sample after reduction with H₂ showed the presence of crystalline copper, which suggests that the copper atoms are held at or near the surface of the carrier.

These studies indicate that the state of cupric ions on alumina supports is not in the form of bulk CuO but in a less defined dispersed state. This dispersed state allows for much higher activity for SO₂ sorption as compared to bulk crystalline CuO.

2.2 CeO₂/Al₂O₃ Catalysts

Little data exists of the structure of CeO₂/Al₂O₃ catalysts. However, the comprehensive study of the structural and catalytic properties of transition metal oxides on alumina conducted by Lo Jacono and Schiavello (1976) showed that the transition metal ions for all transition metals they tested (Mn, Co, Ni, and Cu) behaved in a similar manner. Specifically, they showed that a spinel phase was formed as a consequence of the chemical interaction between a transition metal ion and the large area aluminas both unmodified and modified. This interaction was not limited to support aluminas, but also took place on their oxidic supports. Additionally, they showed that concurrently with the

spinel formation reaction, the segregation of the transition metal occurred at a content of the transition metal ion which depended on the atmosphere of firing.

Hedges and Diffenbach (1990) performed X-ray diffraction tests on fresh and spent sorbents. Results showed that the CeO_2 on the sulfated sorbent did not exist as crystalline metal, but rather as an amorphous or highly dispersed sulfate. FTIR comparisons of the fresh and spent sorbents showed the presence of sulfates, but not in the form of bulk $\text{Ce}(\text{SO}_4)_3$. These results are consistent with those of most transition metal oxides.

It is therefore likely that the cerium ions exist in the much the same for as the copper ions, not in the form of bulk CeO_2 but in a less defined dispersed state. This dispersed state allows for much higher activity for SO_2 sorption as compared to bulk crystalline CeO_2 .

3.0 Mechanism of SO_2 Sorption

3.1 SO_2 Sorption on Alumina Supported CuO

Although McCrea *et al.* (1970) proposed the chemical reaction for the SO_2 sorption on alumina supported CuO as:

for freshly prepared and used sorbent samples, X-ray diffraction shows neither crystalline CuO (see above discussion) or CuAl_2O_4 in the fresh samples, nor crystalline CuSO_4 in the used samples [Centi, (1990, 1992); Friedman *et al.* (1978); Kent *et al.* (1977); Lo Jacono and Schiavello(1976); Pollack *et al.* (1988); Waqif *et al.* (1991), Yoo *et al.* (1994)]. The copper atoms dispersed on the surface of the support materials are not in a well-defined form.

Hao and Cooper (1994) used a sequence of extended surface (band structure) and cluster method total-energy calculations to model the process of SO_2 adsorption on the $\text{CuO}/\text{Al}_2\text{O}_3$ surface. The band calculation indicated that the copper atoms are adsorbed at oxygen-octahedrally-coordinated sites of the $\text{CuO}/\text{Al}_2\text{O}_3$ surface and that, as expected, the Cu-O bonding is not as strong as the Al-O bonding. The calculations showed that the SO_2 is probably adsorbed on the surface via O-Cu bonding in the form of a bridge with the two oxygen atoms of SO_2 sitting at two surface metal atoms. They also concluded that low temperature adsorption is preferable to make the adsorbent reusable because of the lower bonding energy of the O-Cu bonding.

Based on their observation of the absence of bulk CuO on the fresh sorbent and bulk of CuSO_4 on the sulfated sorbent, Centi *et al.* (1990) postulated the following surface mechanism for the DeSOx reaction:

1. SO_2 is chemisorbed on lattice oxygen of the sorbent-catalyst

2. copper catalyzes the oxidation of SO₂ with the lattice oxygen to SO₃, but the SO₃ does not desorb in the gas phase and remains linked to the surface as an S-bonded chemisorbed species
3. the SO₃ in turn reacts with a further copper site forming a bidentate copper-sulfate surface species characterized by a low symmetry that passivates the active surface
4. if neighboring support sites are present, a transfer of the sulfate group to the support may occur to form a surface sulfate species linked to Al, with fast regeneration of the active copper surface in the presence of gaseous oxygen, therefore making it possible for the DeSOx reaction to continue.

This reaction depends on the rate of surface diffusion, and therefore the relative rate of the reaction with copper or support sites is affected considerably by the reaction temperature.

3.2 SO₂ Sorption on Alumina Supported CeO₂

In a similar manner to McCrea *et al.* (1970), the equation for the sulfation of alumina supported CeO₂ is often written as:

However, it is unlikely that crystalline CeO₂ exists on the fresh sorbent or bulk Ce₂[SO₄]₃ on the sulfated sorbent. Studies of the structure of transition metals and transition metal sulfates show that the metal is in a highly dispersed amorphous phase, and the sulfate is adsorbed to the metal sites without forming a bulk metal sulfate. X-ray diffraction and Fourier transform infrared spectroscopy (FTIR) studies have indicated that CeO₂/Al₂O₃ sorbents are consistent with this structure (Hedges and Diffenbach, 1990).

3.3 Postulated SO₂ Adsorption Path

Following the postulated adsorption path of Centi *et al.* (1994), the basic phenomena occurring in metal oxide/SO₂ systems may be represented by a strictly bivalent metal, in a simplified manner, by the following equations (Koballa and Dudukovic, 1978)

The SO_2 molecules are chemisorbed on the active sites of the metal oxide forming an unstable sulfite ion (or surface complex of a similar form) as indicated by Equation (2). This active complex may stabilize itself into a sulfite or may be oxidized with the adsorbed oxygen (or gas phase oxygen) to a sulfate form (Lowell *et al.*, 1971; Glass and Ross, 1971; Dixon and Longfield, 1960; Krause, 1962). Sulfate formation is favored on all transition group metal oxides, but the extent of sulfate buildup and its stability depend on the temperature of the system. In a temperature range below sulfate decomposition, temperature adsorption [Equations (2) and (3)] accompanied by non-catalytic gas-solid reaction [Equation (4)] occurs predominantly. Only small amounts of sulfite are possibly formed by reaction (5). Thus, in a certain temperature range all metal oxides behave as adsorbents for SO_2 , the reaction pathway may be described by Equations (2) to (4), and a surface sulfate is observed. At high temperatures (not necessarily above sulfate decomposition temperature) metal oxides exhibit, in general, the following catalytic activity:

If the temperature is above sulfate decomposition temperature, this may imply that the preferred reaction path shifts in favor of reactions described by Equations (2), (3), (6), and (8), in which case only a small sulfate buildup would occur (Glass and Ross, 1971). At even higher temperatures it is conceivable that sulfate is an intermediate and that the reaction path proceeds along the line described by Equations (2), (3), (4), and (7).

Sulfite and sulfate formation is thermodynamically feasible (Lowell, 1971) and has been observed experimentally (Glass and Ross, 1971). But there is little information on the character of the intermediate complexes. It is also not clear whether adsorbed oxygen, metal oxide oxygen, or gas phase oxygen participates in the reaction with SO_2 (Glass and Ross, 1971; Mars and Maessen, 1968; Regner and Simecek, 1968). Based on the analogy with CO oxidation, one could suggest that it is the adsorbed or metal oxide oxygen (depending on the type of oxide used) that participates in the reaction (Gravelle and Teichner, 1958; Winter, 1958; Stone, 1962).

The actual reaction mechanism in the case of a multivalent metal is much more complex than the simplified model discussed above. Such a mechanism would involve: multiple oxidation states, sulfite formation, sulfate formation, disproportionation of sulfites to sulfates and sulfides, sulfate decomposition, sometimes via oxysulfates, and catalytic oxidation of SO_2 . However, for engineering purposes, the process may be viewed as consisting of the following main steps:

1. Sorption of SO_2 and formation of sulfite
2. Oxidation of sulfite to sulfate
3. Sulfate decomposition with evolution of SO_3

At high enough temperatures all three steps occur as surface reactions in sequence, and metal oxides behave as catalysts.

Only the first two steps will occur at lower temperatures when metal oxides simply adsorb SO_2 and O_2 and are converted to surface sulfates. It was observed (Lowell *et al.*, 1971), at least qualitatively, that metal oxides behaved as catalysts above their sulfate decomposition temperature, while below that temperature little or no catalytic activity was detected.

In possible applications of metal oxides the reaction mechanisms and kinetics are even further complicated by the fact that the flue gas is a complex mixture containing components such as CO , CO_2 , H_2O , NO , which may react with metal oxides or be catalyzed by them. Commercial adsorbents and/or catalysts consist of metal oxides on support. The nature of the support and its preparation may affect considerably the properties of these adsorbents and make their behavior in SO_2 adsorption/oxidation different from the one observed with pure metal oxides.

4.0 Previous Experimental Studies of Sulfation Kinetics

The investigations to date can be divided into two main categories:

1. Studies of bulk CuO , CeO_2 , and various metal oxides as possible adsorbents for SO_2 from flue gas
2. Studies of supported metal oxides for SO_2 removal.

The latter category can be subdivided further into absorption and adsorption studies. A summary of the major investigations is given below.

4.1 Unsupported Metal Oxides

Bienstock and Field (1960) did an extensive screening study for the US Bureau of Mines to identify the solids which would be good potential adsorbents or catalysts for SO_2 in flue gases. Their results with bulk metal oxides of interest are summarized in Table 1.

Table 1: Results of Bienstock and Field Screening Study

Adsorbent	Purity (weight %)	$\frac{SO_2 \text{ adsorbed}}{\text{g adsorbent}}$	Temperature, °F
Co_3O_4	97	0.25	266
Co_3O_4	97	0.47	626
Co_3O_4	100	0.12	266
Co_3O_4	100	0.44	626
CuO	99	0.01	266
CuO	99	0.56	626
CuO on alumina	2.6 - 8.2	0.04 - 0.08	572
$\alpha - Fe_2O_3$	93	0.03	266
$\alpha - Fe_2O_3$	93	0.03	626
$MnO_{1.88}$	90	0.33	266
$MnO_{1.88}$	90	0.23	266
$MnO_{1.88}$	90	0.53	626
$\gamma - Mn_2O_3$	96	0.19	626
$\gamma - Mn_2O_3$	96	0.58	626
NiO	91	0.09	266
NiO	91	0.09	626
NiO	90	0.06	266
NiO	90	0.07	626

It was found that oxides of manganese, cobalt, and copper were the most active as adsorbents and that their capacity increased with temperature. CuO and PbO_2 were only active at the higher temperature; NiO and alkalinized alumina had the same adsorption capacity at both temperatures. An important result of their study was to demonstrate the extreme importance of the method of adsorbent preparation on its capacity. For example copper oxide prepared by the action of sodium carbonate on copper sulfate (0.89 g/cm^3) showed no activity toward SO_2 . It was also reported that thermal regeneration of metal oxide adsorbents by sulfate decomposition at temperatures above 1300°F usually resulted in inactive oxides, while regeneration with reducing gases at 1100°F and lower rendered active oxides.

Lowell *et al.* (1960) attempted to select, on the basis of thermodynamic arguments, from 47 pure metal oxides those which are most promising for a thermally regenerable process. For metals having multiple oxidation states, stable forms were evaluated for the temperature range of interest and at oxygen concentration levels of about 3 percent. They concluded that formation of sulfites under flue gas conditions occurs in competition with sulfate formation. Once formed, a sulfite can decompose by solid state disproportionation to sulfate and sulfide, or it can dissociate to give metal oxide and SO_2 . The authors concluded that formation of sulfates appears to be most likely and that the extent of sulfite formation will be small and will depend on the availability of oxygen and on the rates of the two processes. Oxides of Al, Bi, Ce, Co, Cr, Cu, Fe, Hf, Ni, Sn, Th.

Ti, V, U, Zn, and Zr were selected as the most promising for SO₂ removal in a thermally regenerable process.

DeBerry and Sladek measured the rates of sorption of SO₂ from a flue gas by 14 bulk metal oxides. The oxides were selected based on their predicted applicability to processes for removing SO₂ from a flue gas using thermal regeneration of the sorbent. Measurements were performed using thermogravimetric analysis on samples which were ground and sieved to size range -170 to + 325 mesh. Rates were fitted to semi-empirical expressions. CuO and CeO₂ showed the highest rates. Table 2 summarizes the results for metal oxides which displayed significant SO₂ reduction capabilities.

Table 2: Results of DeBerry and Sladek Study

Oxide	Range of T (oF)	n	Reaction Rate	A (1/min-atm)	E (kJ/mole)
CeO ₂	380 - 500	2	$r = k'(1-\alpha)^n$	2.6E4	33.0
Co ₃ O ₄	675 - 800	1	$r = k'(1-\alpha)^n$	1.6E5	58.1
Cr ₂ O ₃	635 - 735	-	$r = k' \frac{(1-\alpha)^{1/3}}{1 - (1-\alpha)^{1/3}}$	1.9E3	39.4
CuO	620 - 900	1/3	$r = k'(1-\alpha)^n$	4.3E9	112.5
Fe ₂ O ₃	650 - 750	1/3	$r = k'(1-\alpha)^n$	3.3E3	38.3
NiO	720 - 935	1/2	$r = k'(1-\alpha)^n$	7.8E3	56.5
$k_1 = A \exp [-E/RT] = k'/p_{SO_2}$					

Bulk metal oxides do not typically provide sufficient surface area for the desulfurization reaction and tend to sulfate at a slower rate than supported metal oxides. Additionally, bulk metal oxides tend to break up under continuous sulfation/regeneration due to the large molecular size of the surface sulfate compared to the MeO sites. Hence alumina-supported metal oxides are adopted for their high surface areas and pore volumes.

4.2 Supported Metal Oxides

4.2.1 Absorption Models

McCrea *et al.* (1970) investigated SO₂ absorption on copper oxide impregnated into alumina at 575 °F. The sorbent saturation capacity and the width of the transfer zone were determined from the breakthrough curves obtained by the use of an integral bed. The sorption capacity varied and was highest (0.02 - 0.035 g sulfur/g sorbent) for lightly impregnated sorbents (inversely proportional to the width of the transfer zone) and was observed to increase as the second power of temperature indicating that pore diffusion and reaction rate control the overall rate in their 1/16" sorbent. A single step absorption equation was postulated and is given as Equation (1).

Vogel *et al.* (1974) evaluated a number of impregnated metal oxides supported on alumina for removal of SO₂ at 650 °F. A fixed-bed flow reactor was used with the effluent monitored for SO₂ removal by infrared analysis. A kinetic treatment of the system was developed and rates of SO₂ sorption were calculated. A 5 percent SO₂ breakthrough point was chosen for practical rating of the sorbents. The relative capacities of the sorbents were in general agreement with those of bulk oxides in that the alkali and alkaline earth metals were superior in reactivity. Table 3 summarizes their findings.

Table 3: Results of Study by Vogel

Alumina-supported sorbent	Loading, grams SO ₂ /100 cc sorbent		Rate constant, 1/min	% Metal Reacted	
	5 % capacity	Maximum capacity		5 % capacity	Maximum capacity
9.2% Na	8.69	9.94	1130	89	102
BM	7.94	20.3	200	27	69
17.6% Sr	6.59	8.58	620	7	87
12.8% Cu	5.29	6.85	550	62	79
8.0% Ca	4.19	5.23	650	47	59
7.0% Cr	4.01	4.82	770	46	55
27.4% Ba	2.44	3.16	600	26	34
41.4% Pb	1.81	2.72	510	15	23
22.4% Cd	1.27	1.74	560	13	18
5.5% Mn	0.98	1.38	430	11	16
4.8% Mg	0.81	1.08	520	9	12
7.5% Fe	0.72	1.21	330	8	13
6.0% Sc	0.65	0.96	400	7	11
11.8% Co	0.50	0.65	600	5	7
11.8% Ni	0.49	0.69	430	6	8
13.0% Zn	0.28	0.47	360	3	5
16.5% Sb	0	0	-	0	0
4.1% V	0	0	-	0	0
Al ₂ O ₃	0	0.38	-	-	-

Yates and Best (1976) developed a two-step consecutive mechanism for the reaction of SO₂ with copper oxide dispersed on particles of alumina leading via cupric oxysulfate (CuO·CuSO₄), to cupric sulfate:

The resultant equation for the SO₂ breakthrough was fitted to experimental data via a 2-parameter curve fitting technique in order to determine the rate constants for the two steps. The rate coefficients of the two reactions were found in terms of the pre-exponential factors A_i, and the activation energies E_i. Table 4 summarizes the results.

Table 4: Rate Constant Data for the Two-Step Mechanism of Yates and Best

	Reaction 1	Reaction 2
A, 1/s	550.1	17.62
E, kJ/mol	36.79	14.54

Several researchers have evaluated rate constants for the absorption of supported copper oxide based on the equation of McCrea (see Equation 1). The most extensive investigation has been carried out by the US Department of Energy (Yeh *et al.*, 1982; McArdle *et al.*, 1985, Yeh *et al.*, 1987). Other investigations using the one step absorption equation were conducted by Kiel *et al.* (1992), although they used silica rather than alumina as their substrate.

These studies characterized the sorption of SO₂ as an absorption process and defined the rate of consumption of active copper sites by a first order rate equation:

$$\frac{dY}{dt} = k(1 - Y)^n p \quad (12)$$

A microbalance was used in both the Yeh and Kiel experiments to determine the rate constant, k, in the form of an Arrhenius relation. Results of these experiments are given in Table 5.

Table 5: Results of One-Step Absorption Models, CuO/SO₂

Researcher	A, 1/sec	E, kJ/mol	Sorbent Size, mm
Yeh <i>et al.</i> , 1982	13.1	20.1	1.6
Kiel <i>et al.</i> , 1993 - narrow pore	2.26E6	86	1.5
Kiel <i>et al.</i> , 1993 - wide pore	6.5E7	103	1.5

The activation energies for the reactions are significantly different. The activation energies for the experiments by Kiel *et al.* are closer to the value found by DeBerry and Sladek for bulk CuO. This indicates that the support has a significant impact on the state of the supported copper and, therefore, on the rate of sulfation, and suggests that a simple one step absorption reaction is inappropriate. Moreover, Centi *et al.* (1992) attempted to use a one step first order rate equation for the sulfation of copper, and found that the model did not agree with their experimental data or their analyses of the sulfated sorbent.

Much less data is available for the sorption kinetics of SO₂ on alumina supported cerium oxide. The most extensive studies have been carried out by the U.S.

Department of Energy (Hedges and Diffenbach, 1990; Hedges and Yeh, 1991; Hedges and Yeh, 1992; Hoffman *et al.*, 1992). As was the case with the CuO studies, the sorption of SO₂ was characterized as an absorption process and the rate of active copper site consumption was defined by a first order rate equation:

$$\frac{dC_{Ce}}{dt} = kC_{Ce}^m P_{SO_2}^n \quad (13)$$

where C_{Ce} is the concentration of active cerium sites, P_{SO₂} is the partial pressure of SO₂ in kPa, and k is the rate constant in 1/kPa-s.

A microbalance was used in their experiments to determine the rate constant, k, in the form of an Arrhenius relation. Results of these experiments along with the kinetic data of Akyurtlu (1996) provided in conjunction with this report are given in Table 6.

Table 6: Results of One-Step Absorption Models, CeO₂/SO₂ (9% wt. Ce on Sorbent)

Researcher	A, 1/kPa-s	E, kJ/mol	Sorbent Size, mm
Akyurtlu, 1996	0.0192	17.0	ground
Hedges and Yeh, 1992	0.0156	12.0	1.6

An interesting result of the DOE study was that the rate constant depended on the initial concentration of cerium on the sorbent (i.e., their rate constant was not really constant). This resulted in a redefinition of the rate constant as:

$$k' = kC_{Ce_0} \quad (14)$$

where the value of the frequency factor, A, is 0.14 %Ce/kPa-s. This result indicates that the concentration of cerium on the sorbent significantly impacts the cerium ion structure on the alumina. This is not inconsistent with the studies of CuO/Al₂O₃ sorbents where the structure of the sorption sites changed with copper loading. At low concentrations, the metal enters the defect spinel of the γ-alumina support to yield a well dispersed phase which is not detected by X-ray diffraction. The support capacity for γ-aluminas appears to be about 4 - 5 percent by weight for copper per 100 m²/g (Selwood and Dallas, 1948). In this dispersed phase, even up to the highest copper loading, the ions are not in microcrystals of metal oxide. The metal ion locations and interactions with each other differ widely from the bulk material. After the adsorption sites of the support are saturated, a discrete crystalline phase of clustered metal oxide forms on the surface. For copper oxide, this begins at about 10 - 11 percent by weight (Strohmeier *et al.*, 1985). It appears likely that in the DOE studies the sorbents with higher cerium loadings had lower rate constants because of the formation of bulk crystalline CeO₂.

As is apparent from the above discussion, the structure of the metal oxide on the substrate is critical in predicting the sorbent performance. While detailed analyses exist for CuO sorbents, more investigation of the phases of cerium on alumina is

required before accurate predictions of sorbent performance at varying cerium concentrations can be made.

4.2.2 Adsorption Models

Kent *et al.* (1977) studied the adsorption of SO₂ on copper (II) oxide. They found that the adsorption of small amounts of sulfur dioxide at 675 °F resulted in the formation of surface sulfates. Further adsorption at 675 °F produced a bulk sulfate (SO₄). The postulated surface reaction leading to sulfate formation was:

The removal of the water exposes a surface copper ion and adsorption on this site was thought to form a sulfite group.

No bulk *copper* sulfate was found; all reactions were assumed due to adsorption mechanisms.

Cho and Lee (1983) developed an expression for the SO₂ breakthrough curve based on the adsorption mechanism postulated by Equations (2), (3) and (4) and assuming two of the three steps are in equilibrium, and only one is rate determining. The alumina support was 3/16" x 1/18" tablet type porous γ-alumina which was impregnated with copper to 5 percent (weight) by soaking the tablets in a solution of copper nitrate. The SO₂ breakthrough was fitted to experimental data via a 2-parameter curve fitting technique in order to determine the rate coefficients for consumption of active copper sites and the overall reaction rate. The rate coefficients were found in terms of the pre-exponential factors A_i, and the activation energies E_i.

Uysal *et al.* (1988) postulated the same mechanism as Cho and Lee to characterize CuO on activated alumina. In their experiments, 0.0187" alumina was impregnated with CuO by immersing the alumina particles in a copper nitrate solution. The procedure gave about 6 percent by weight Cu on the sorbent. Table 7 presents the results of Cho and Lee (1983) and Uysal *et al.* (1988).

Table 7: Results of Cho and Lee vs. Uysal *et al.*

	Cho and Lee (1988)		Uysal <i>et al.</i> (1988)	
	Rate of Copper Site Consumption	Overall Reaction Rate	Rate of Copper Site Consumption	Overall Reaction Rate
A, 1/min	0.156	560.96	0.122	2.36E6
E, kJ/mol	3.43	8.314	0.8515	29.4
r, 1/min at 650 K	0.0827	120.4	0.105	1.02E4

Note the large differences in the predicted rate constants. The differences are most likely due to the different experimental setups and substrates. Cho and Lee measured the kinetic parameters by using a 1.5 cm diameter, 13 cm long tube furnace. Uysal *et al.* used a 5 cm diameter, 40 cm long tube operated as a bubbling bed. The model for the differential tube furnace is based on well known physics, while the bubbling bed model is rather speculative and simplistic. Therefore the Cho and Lee data is probably more representative of the true rate constants. It is also possible that there was significant diffusional resistances in the relatively large tablets of Cho and Lee resulting in the smaller overall reaction rates.

Centi *et al.* (1992) performed extensive analyses on the mechanism of SO_2 oxidation-adsorption and the kinetics of the adsorption. They found that the best fit kinetic results for a reaction model involved a first step of oxidation of chemisorbed SO_2 to chemisorbed SO_3 on copper followed by further reaction of the chemisorbed SO_3 ,

1. with a second neighboring copper species to form a sulfate species linked to copper, or
2. a surface transfer to neighboring Al species to form sulfate species linked to Al.

The reaction model was in good agreement with reactivity and spectroscopic evidence on the reaction mechanism, and with the mechanism postulated by Koballa and Dudukovic (1978) (see Equations 2 through 4).

5.0 Summary

Based on a review of available literature, there is strong evidence to support the theory that the sulfation of alumina supported MeO is an adsorption process; specifically chemisorption. The absence of bulk MeO in the regenerated sorbent and bulk Me-SO_4 in the sulfated sorbent provide the most convincing evidence. Additionally, differences in sulfation kinetics between substrates, along with the much lower activation energy as compared to the sulfation of bulk MeO casts doubt on the validity of a one-step chemical reaction. A more thorough argument supporting this claim is given in Appendix A. The following Section describes the adsorption model used to evaluate sorbent and adsorber performance.

6.0 Adsorption Kinetics

The performance of a bed of sorbent in which adsorption takes place is described by two sets of equations. The first set consists of the differential over-all and component material balances on the gas and solid phase and contains a global rate expression, which is either empirically obtained or derived from the postulated models for point rate processes. The second set of equations deals with the point rate processes and resistance's and usually contains conservation equations for a single pellet and

constitutive equations describing the local rates. It is understood that several steps may affect the overall rate of the process. These steps are:

1. External (fluid phase) transfer: the mass transfer by diffusion and convection of the SO_2 from the bulk fluid to the outer surface of the solid particle.
2. Internal transfer: transfer of the SO_2 to the interior of the solid particle by
  - a. Diffusion through pores - in which case the SO_2 diffuses through the fluid filled pores in its original form;
  - b. Solid-phase diffusion - in which case the SO_2 is transferred in its adsorbed form either via surface diffusion along the pores' walls or via volume diffusion through holes in the chemical structure of the solid
3. Adsorption-desorption at the active sites: some of the collisions of the SO_2 molecules with the active sites on the solid exterior and/or interior walls of the pores result in adsorption, i.e., in transformation of SO_2 to its adsorbed state or surface complex.
4. Chemical reaction on the solid: the SO_2 in the adsorbed state undergoes a chemical reaction (i.e., and additional transformation) either with the solid or with another component from the fluid phase or with another adsorbed component.
5. In case of a reversible process, steps 1 and 4 will apply in the reverse order to the reaction product.

In addition, heat transfer processes may be of great importance in affecting the overall rate. However, for small SO_2 concentrations and relatively small heats of adsorption, the assumption of isothermality is usually acceptable.

It is of interest to note that most investigators do not distinguish between steps 3 and 4 and tend to lump them together. Although the adsorption step may be viewed as a reaction, often only an intermediate complex is formed first which is subject later on to further transformations. The above classification is more meaningful since it allows the interpretation of all related but different phenomena in the view of the presently available theories and models. Without step 4, one can cover the phenomena of adsorption and chromatography; with step 4, if the reaction takes place with the solid, the area of fluid-solid non-catalytic reactions can be analyzed, and, if the reaction takes place with another fluid or adsorbed component, catalytic properties can be studied. The adsorption process is ignored (assumed infinitely fast) in the treatment of fluid-solid reactions while it is emphasized for catalytic reactions when step 4 is often neglected. Yet the two phenomena are closely related, as has been demonstrated with the systems SO_2 , O_2 , and metal oxides, and the difference results from the reaction path of the SO_2 in the adsorbed state.

In summary, for proper interpretation or prediction of breakthrough curves it is necessary to:

1. Apply conservation equations to an element of the bed for fluid and solid phase, and
2. Establish the point kinetics and rate coefficients of the various rate processes and evaluate the equilibrium isotherm.

7.0 Governing Equations

The mass balance equation for the adsorbable component (SO_2) in the direction of flow is:

$$D_{af} \frac{\partial^2 C}{\partial z^2} - u_o \frac{\partial C}{\partial z} - (1-\epsilon) \rho_p \frac{\partial q}{\partial t} = \epsilon \frac{\partial C}{\partial t} \quad (17)$$

where

C = adsorbate concentration in the gas phase

ρ_p = density of the adsorbent

D_{af} = axial dispersion coefficient

u_o = superficial fluid velocity

ϵ = bed void fraction

q = number of moles adsorbate per unit weight of adsorbent

The rate of adsorption is controlled by the step which exerts the greatest resistance to transfer and is inherently the slowest. The mathematical solution is simplified by neglecting all resistance's but the rate controlling one or by combining all the steps into one effective step with a single apparent rate. The forms of the rates for various steps which are rate controlling are presented in Table 8. It is also necessary to know the relationship between the adsorbate (SO_2) in the adsorbed and free state (the adsorption isotherm)

$$q_s = f(C_s) \quad (18)$$

Table 8: Rate Expressions for Rate Controlling Steps in Adsorption Process

Controlling Step	Rate Expression
External Mass Transfer	$\rho_s \frac{\partial q}{\partial t} = k_f a_p (C - C_s)$
Surface Reaction	$\frac{\partial q}{\partial t} = k_1 C (Q - Q_s) - k_2 q$
Internal Diffusion - Solid Phase Diffusion	$\frac{\partial q}{\partial t} = \frac{D_s}{r^2} \frac{\partial}{\partial r} \left(r^2 \frac{\partial q}{\partial r} \right)$
Internal Diffusion - Pore Diffusion	$(1-\epsilon) \rho_s \frac{\partial q}{\partial t} = \frac{D_p}{r^2} \frac{\partial}{\partial r} \left(r^2 \frac{\partial c_i}{\partial r} \right) - \epsilon \frac{\partial c_i}{\partial t}$

In the theory of chromatography, it is often assumed that all the rate steps are infinitely fast and that equilibrium between the gas and solid phase exists at every point in the column. For an irreversible adsorption, this would result in a step-up breakthrough curve. Since such behavior is not observed in SO₂-metal oxide systems, these models were not treated further.

In order to determine the rate controlling mechanism(s), order of magnitude estimates for the resistance's need to be determined. Table 9 presents the expressions for the various resistance's.

Table 9: Resistance Expressions for Various Rate Controlling Mechanisms

Controlling Step	Resistance Expression (s/cm)
External Mass Transfer	$\frac{1}{k_f}$
Surface Reaction	$\frac{a_p}{k_r}; a_p = \frac{6(1-\epsilon)}{d_p}$
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\epsilon)}; \Lambda \approx O(10^3)$
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p} = \frac{10D_p}{d_p}$

Values for the various resistance's have been determined and are presented in Tables 10 and 11.

Table 10: Values for Rate Controlling Resistances - CuO

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	0.17	0.13	0.10
Surface Reaction	$\frac{a_p}{k_r}; a_p = \frac{6(1-\varepsilon)}{d_p}$	4.34	8.68	17.3
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\varepsilon)}; \Lambda \approx O(10^3)$	3.5	1.74	0.87
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.90	0.45	0.23
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_\kappa}; k_\kappa = \frac{10D_\kappa}{d_p}$	6.35	3.17	1.59

Table 11: Values for Rate Controlling Resistances - CeO₂

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	0.15	0.12	0.090
Surface Reaction	$\frac{a_p}{k_r}; a_p = \frac{6(1-\varepsilon)}{d_p}$	32.1	64.2	128.4
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\varepsilon)}; \Lambda \approx O(10^3)$	3.5	1.74	0.87
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.66	0.33	0.165
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_\kappa}; k_\kappa = \frac{10D_\kappa}{d_p}$	5.20	2.60	1.30

For the 1/4" and 1/8" copper oxide sorbent particles, surface reactions, internal solid phase diffusion, and Knudsen diffusion all appear to contribute to the adsorption kinetics. For the 1/16" CuO sorbent, surface reactions dominate the resistance. In the case of the cerium oxide sorbents, the surface reaction always controls the adsorption kinetics

Thus, the adsorption model (Equation 15) needs to be solved in combination with three different resistance expressions for the CuO system (solid phase diffusion, Knudsen diffusion, and surface reactions) and one for the CeO₂ system (surface reactions).

8.0 Modeling Large Batch or Moving Bed Reactors

Once the rate constant and saturation capacity of the sorbent are known, Equations (15), and (16) along with the appropriate equations in Table 7 can be solved to yield the SO₂ breakthrough curve for any batch reactor.

A moving bed reactor can also be easily modeled. In a moving bed, the SO₂ outlet concentration will initially increase with time and then approach a steady state limit which will be time independent. A moving bed adsorber can be viewed as a series of vertically differential reactors which extend horizontally across the entire reactor width. The vertical location of each vertical differential section can be converted into a time the differential section has been in the adsorber using the sorbent flow rate (which, given a reactor cross-sectional area, converts to a sorbent velocity). The farther down the differential section is located, the longer it has been in the reactor. For example, a differential section located at a distance 10 feet from the top of a reactor with a cross-sectional area of 40 ft² operating with a solids flow rate of 5000 lb/hr ($\rho_{\text{bulk}} = 50 \text{ lb/ft}^3$) has been in the reactor 4 hours. Since each differential section always sees the same inlet SO₂ concentration. The average SO₂ outlet concentration is simply the time averaged integral of the breakthrough curve:

$$\frac{c_{\text{out}}}{c_0} = \frac{1}{t_{\text{orb, res.}}} \int_0^{t_{\text{orb, res.}}} X(t) dt \quad (19)$$

Equations (15) or (16) and the sorbent point rate process expressions can be substituted into Equation (34) with the appropriate input parameters to solve for the SO₂ concentration in the effluent stream. For a given moving bed configuration and SO₂ flow rate, as the sorbent residence time increases (lower sorbent flow rate), the SO₂ outlet concentration increases, and vice versa.

9.0 Pressure Drop Determination

The calculation of flue gas pressure drop through the moving bed was accomplished by modeling the moving bed as a fixed bed, evaluating the gas properties at the bed inlet, and using the well known Ergun equation (1952)

$$\frac{\Delta P}{L} g_c = 150 \frac{(1-\epsilon)}{\epsilon^3} \frac{\mu u_o}{(\Psi d_p)^3} + 1.75 \frac{(1-\epsilon)}{\epsilon^3} \frac{\rho_f u_o^2}{(\Psi d_p)} \quad (20)$$

where

$\Delta P/L$ = pressure drop per unit length of bed, lb/ft³

g_c = gravitational constant, ft/lb-sec²

ε = bed void fraction

Ψ = sorbent particle sphericity

ρ_f = gas density, lb/ft³

10.0 Model Input Assumptions

Several parameters are required as inputs to the model. The number of inputs depends on how many of the point rate process are important. In the case of the CeO₂ sorbents, only inputs related to the surface reaction process are required, since this process dominates the kinetic resistances. For the larger CuO sorbents, more inputs will be required since diffusional processes are important. A summary of the general input parameters are given in Table 12. Inputs specific to the CeO₂ and CuO sorbents are given in Table 13.

Table 12: General Model Input Parameters

Parameter	Value	Basis
Gas Flow	3,000,000 (lb/hr)	Approximate value for a 400 MWe pulverized coal power plant
Inlet SO ₂ concentration	3000 (ppm)	Typical SO ₂ concentration in flue gas of high sulfur coal
Adsorber Height	45 feet	Sorbent flow and mechanical constraints
Adsorber Width	10 feet	Sorbent flow and mechanical constraints
Sorbent Density	60 lbs/ft ³	Typical for Alcoa alumina sorbents
Sorbent Voidage	0.45	Typical for Alcoa alumina sorbents
Average Pore Diameter	90 angstroms	Typical for Alcoa alumina sorbents
Reaction Stoichiometry - based on complete metal site useage	1.2	Optimal based on reactor sizing, excess sorbent, and excess regenerator gas required
Required Removal Efficiency	98 %	Efficiency required to compete with other available technologies
Maximum Allowable Pressure Drop	2" H ₂ O	Required to compete with other available technologies

Table 13: Sorbent Specific Model Input Parameters

Parameter	Value	Basis
Copper Oxide Sorbent		
Metal Loading on Alumina	9.0 percent by wt.	Data available
Maximum SO ₂ Capture	0.62 - 1.0 mole SO ₂ /mole Cu at 700 °F	Experimentally Determined - Sorbent Dependent
Overall Kinetic Rate Constants (surface reactions and diffusional processes)	0.0735 - 0.132/s at 700 °F	Experimentally Determined - Sorbent Dependent
Heat of Sulfation	132,039 Btu/lb-mole SO ₂ reacted	Based on heats of formation
Cerium Oxide Sorbent		
Metal Loading on Alumina	9.0 percent by wt.	Data available
Maximum SO ₂ Capture	2.0 mole SO ₂ /mole Ce	Suggested value from Hampton U.
Surface Reaction Rate Constant (no diffusional effects)	0.162/s at 1022 °F 0.187 at 1112 °F	Experimentally Determined Rate Data by Hampton U.
Heat of Sulfation	126494 Btu/lb-mole SO ₂ reacted	Based on heats of formation

The surface reaction rate constants for the cerium oxide sorbents were adjusted within the model to take into account long term diffusional effects. This was accomplished by adjusting the effective reaction rate by an effectiveness determined by the sorbent fractional conversion and the pore structure of the sorbent. The effective reaction rate constants varied, depending on the sorbent, from about 70 percent to 90 percent of the reaction rate with no diffusional effects present.

It should be noted that the heat of sulfation was based on the heats of formation assuming the metal oxide is converted to bulk metal sulfate. The previous discussion has shown that this is probably not the case. Therefore, the heat of sulfation used in the model may be much larger than the actual heat of adsorption based on a weaker bond between the adsorbed SO₂ and the metal oxide. Actual measurements of the heats of adsorption for the CuO and CeO₂ sorbents, or several adsorption isotherms determined at different temperatures would be required for an accurate prediction of the heat release during the sulfation reaction.

11.0 Sulfation Model Results - Required Number of Adsorber Modules

Table 14 presents the results of the model for the CuO and CeO₂ sorbents.

It is interesting to note that an increase in temperature for the CeO₂ sorbent did not reduce the number of modules required. This is the result of the increase in gas viscosity and decrease in flue gas density. To keep the pressure drop across the bed at 2" H₂O, more frontal area is required. Since most of the cost of the adsorption unit will be in the frontal area of the reactor, as will be shown below, it does not appear to be advantageous to operate at the higher temperature, especially since the cost of the materials of construction will increase significantly.

Overall, there is little difference in the number of modules required for the CuO and CeO₂ sorbents operating at their respective temperatures. The volume of sorbent required for the CuO adsorption unit is higher, which may lead to higher sorbent costs depending on the cost ratio of CuO to CeO₂ sorbent. The higher temperature of the CeO₂ adsorption unit will result in a significant increase in materials of construction costs. Therefore, the tradeoff between the CeO₂ and CuO adsorption units will be between the reduced sorbent volume for the CeO₂ system vs. the reduced construction costs of the CuO system.

Model output of the gas outlet temperature and the SO₂ outlet concentration as a function of adsorber height, and the sorbent outlet temperature as a function of bed width is given in Appendix B. This output used the kinetic data of Akyurtlu (1996) in modeling the CeO₂/SO₂ adsorption, and the kinetic data of Tecogen (1996) in modeling the CuO/SO₂ adsorption.

Table 14: Summary of Model Results for Adsorber

Sorbent	Gas Flow Rate (lb/hr)	Sorbent Flow Rate (lb/hr)	Gas Inlet Temperature (°F)	Sorbent Inlet Temperature (°F)	Gas Outlet Temperature (°F)	Sorbent Outlet Temperature (°F)	Gas Face Velocity (ft/s)	Adsorber Depth (in)	Total Adsorber Volume (ft³)	Total Number of Modules
Copper Oxide Sorbents (650 K)										
1/16"	3,000,000	325,844	700	700	745	710	0.49	11.75	46,667	106
1/8"	3,000,000	325,844	700	700	745	710	0.73	28	75,000	72
1/4"	3,000,000	325,844	700	700	746	709	1.15	50	85,417	46
Cerium Oxide Sorbents (823 K) - Kinetic Data of Akyurtlu (1996)										
1/16"	3,000,000	553,030	1022	1022	1050	1044	0.61	7.8	31,850	109
1/8"	3,000,000	553,030	1022	1022	1056	1042	1.04	16	38,625	65
1/4"	3,000,000	553,030	1022	1022	1057	1042	1.70	28	41,250	40
Cerium Oxide Sorbent (873 K) - Kinetic Data of Akyurtlu (1996)										
1/16"	3,000,000	553,030	1112	1112	1140	1134	0.66	6.9	27,563	107
1/8"	3,000,000	553,030	1112	1112	1143	1132	1.12	14.15	28,500	64
1/4"	3,000,000	553,030	1112	1112	1146	1132	1.82	24.75	36,094	39
Cerium Oxide Sorbents (823 K) - Kinetic Data of Hedges and Yeh (1992)										
1/16"	3,000,000	553,030	1022	1022	1050	1044	0.78	6.0	19,150	86
1/8"	3,000,000	553,030	1022	1022	1053	1043	1.31	12.0	23,000	52
1/4"	3,000,000	553,030	1022	1022	1056	1042	2.07	20.5	24,800	33
Cerium Oxide Sorbent (873 K) - Kinetic Data of Hedges and Yeh (1992)										
1/16"	3,000,000	553,030	1112	1112	1135	1135	0.82	5.35	17,388	87
1/8"	3,000,000	553,030	1112	1112	1142	1133	1.39	11.0	21,083	52
1/4"	3,000,000	553,030	1112	1112	1145	1132	2.20	18.75	22,672	33

12.0 Regeneration Modeling of Me-SO₄

In a metal oxide flue gas cleanup process, the sulfated sorbent is regenerated in a moving bed reactor. Because the sorbent in the regenerator is ash free, and the regeneration gas superficial velocity is very low, a counterflow adsorption column is the most economical vessel for regeneration of the spent sorbent.

Several gases can be used to regenerate the Me-SO₄ to Me. The most commonly used gases are methane, hydrogen, and synthesis gas (H₂-CO mix). Only methane and hydrogen will be evaluated as part of this study.

12.1 Me-SO₄ Regeneration Studies

Rate data on the regeneration of metal sulfates by reducing gases is scarce. The U.S. DOE has conducted a preliminary study of the regeneration kinetics of a 1/16" alumina supported CuO sorbent using hydrogen, methane, and synthesis gas (Yeh *et al.*, 1982; Markussen and Pennline, 1993; Markussen *et al.*, 1994; Harriott and Markussen, 1992). Additional kinetic studies of Cu-SO₄ on alumina reduction using methane and hydrogen has been conducted by Tecogen (Hyre *et al.*, 1996). A summary of these results is given in Table 15.

Table 15: Results of Cu-SO₄ Regeneration Studies

Researcher	A, 1/sec	E, kJ/mol	Sorbent Size, mm
Hydrogen Reduction			
Yeh <i>et al.</i> , 1982	1.77	11.5	1.6
Tecogen, 1996	0.082	8.98	1.6, 3.2, 6.5
Methane Reduction			
Yeh <i>et al.</i> , 1982	1.40E5	108.6	1.6
Markussen <i>et al.</i> , 1994	3.95E5	110.8	1.6
Tecogen, 1996	2.66E8	152.1	1.6, 3.2, 6.5

The activation energies for copper sulfate regeneration by hydrogen are much lower than that for the regeneration of unsupported and silica supported copper sulfate. Table 16 compares the activation energies for supported and unsupported copper sulfate regeneration.

Table 16: Comparison of Hydrogen Regeneration Activation Energies for Supported and Unsupported Cu-SO₄

Researcher	E, kJ/mol	Supported or Unsupported
Hydrogen Reduction		
Kiel et al., 1992	74	Silica Supported
Vo Van and Habashi, 1974	62 - 70	Unsupported
Yeh <i>et al.</i> , 1982	11.5	Alumina Supported
Tecogen, 1996	8.98	Alumina Supported

Table 16 provides further evidence that the support plays a large factor in the structure of the Cu-SO₄.

No kinetic data in the open literature exists for the regeneration of Ce-SO₄. Hedges and Diffenbach (1990) studied the effect of regeneration with methane and hydrogen on the SO₂ uptake on CeO₂/Al₂O₃ sorbents. They noted that regeneration with methane proceeded at a much slower rate than with hydrogen. Raising the temperature by 90 °F when regenerating with methane increased the reaction rate to nearly the same as that with hydrogen at the lower temperature (1112 °F).

Akyurtlu (1996) has provided kinetic data for the regeneration of Ce-SO₄ as part of this investigation. Table 17 summarizes his results:

Table 17: Results of Ce-SO₄ Regeneration Studies

Researcher	A, 1/sec	E, kJ/mol	Sorbent Size, mm
Hydrogen Reduction			
Akyurtlu, 1996	1.77	11.5	ground
Methane Reduction			
Akyurtlu, 1996	1.40E5	108.6	ground

12.2 Effect of SO₂ Concentration on Regeneration Kinetics

Several investigators have noted that methane-Cu-SO₄ regeneration kinetics are strongly influenced by the presence of SO₂. The CH₄ regeneration reaction with SO₂ present does not proceed to completion and the reaction rate is slowed significantly (Markussen *et al.*, 1994; Harriott and Markussen, 1992; Centi *et al.*, 1995). Langmuir-Hinshelwood kinetic expressions were developed to describe the regeneration kinetics which took into consideration the effects of SO₂ and equilibrium constants for methane. The resulting expression is:

$$k_1 = \frac{k_2 p_{CH_4}}{1 + K_1 p_{CH_4} + K_2 p_{SO_2}} \quad (21)$$

where the values for k_2 , K_1 , and K_2 were determined at three temperatures. The results are presented in Table 18.

Table 18: Langmuir-Hinshelwood Coefficients as Determined by Markussen *et al.* (1994)

Temperature ($^{\circ}\text{F}$)	k_2 (1/min-atm)	K_1 (1/atm)	K_2 (1/atm)
842	0.71	2.07	8.41
896	1.38	1.56	5.19
950	2.79	2.05	3.00

Akyurtlu (1996) determined the effect of SO_2 on the regeneration of Ce-SO_4 . The rate constant was expressed in terms of the fractional partial pressures of hydrogen and SO_2 :

$$k_1 = \frac{k_2 p_{\text{H}_2}}{(1 + \sqrt{9.23 p_{\text{H}_2}} + 170 p_{\text{SO}_2})^2} \quad (22)$$

Note that in this expression, very small amount of SO_2 in the gas stream has a very large effect on the overall reaction rate. For example, a SO_2 fractional partial pressure of ten percent reduces the reaction rate by nearly a factor of 30.

No data exists on the effect of SO_2 concentration on the hydrogen regeneration of Cu-SO_4 or on the methane regeneration of Ce-SO_4 . Further investigations need to be conducted to discern these effects.

12.3 Hydrogen Consumption During Regeneration

Several investigators have noticed a larger than stoichiometric consumption of hydrogen during the regeneration reaction with pure hydrogen (van der Grift, 1990; Centi *et al.*, 1995; Pennline, 1995). This additional consumption reached as high as 7.5 times the theoretically determined amount with no excess hydrogen detected at the regenerator exit in DOE's CuO moving bed test facility (Pennline, 1995). Investigations were conducted at Tecogen to determine the cause of the additional consumption.

Through tube furnace testing, it was determined that many side reactions prevail when hydrogen is used as the reducing agent, and in particular H_2S also forms. Three paths for hydrogen consumption were identified:

Path 1:

Path 2:

Path 3:

All of these reactions were confirmed in the tube furnace experiments.

Path one is the desired path normally associated with the regeneration of copper sulfate. In path two, copper sulfate is reduced to cupric sulfide, which is further reduced to cuprous sulfide. Thermodynamics predict the reduction of cupric to cuprous sulfide; reduction of cupric sulfide to copper metal does not occur. Under reducing conditions, cuprous sulfide is the most stable compound. The cuprous sulfide present after regeneration cannot be reduced by hydrogen further in the temperature range of interest. The sulfide retained in the sorbent after regeneration is converted to sulfate upon oxidation and adsorption. The formation of copper sulfide during regeneration lowers both the adsorption rate and the capacity, whereas the consumption of reducing agent, per amount of sulfur dioxide removed is increased. Therefore, the amount of cuprous sulfide formed during regeneration of a sulfated sorbent should be minimized.

In path three, the sulfur dioxide released from the sulfated sorbent reacts with the hydrogen reducing gas and is catalytically converted by either Cu or Cu₂S to H₂S and water. This is probably why no excess H₂ was seen in the DOE facility; it had all been converted to H₂S.

Because of the large consumption of H₂ in the regeneration process along with the reduction of the adsorption capacity and rate, H₂ is not currently being pursued as a reducing agent for the copper oxide process. No data exists on the consumption of H₂ during the regeneration of sulfated cerium oxide sorbent. Additional testing is imperative to ensure the adverse side reactions which occur with the sulfated copper oxide sorbent do not also occur during the regeneration of the cerium oxide sorbent.

12.4 Catalytic Oxidation of Methane

The advantage of using methane as the regeneration gas is that SO₂ is the only sulfur-bearing product. The primary drawback of using methane is that the reaction kinetics are very slow, and the reaction is endothermic. One potentially attractive method for increasing the rate of regeneration with methane is to bleed a stream of oxygen in with the methane and allow it to catalytically react over the copper or cerium oxide. Several studies have been carried out on determining the properties of catalysts for the oxidation of methane at temperatures below the ignition point (Anderson *et al.*, 1961; Yant and Hawk, 1927):

Platinum, palladium and the oxides of transition metals such as copper, cobalt, chromium, and vanadium were reported to have catalytic activity. Initial testing at Tecogen has successfully shown that the catalytic oxidation of methane does occur over

the CuO/Al₂O₃ sorbent while regenerating, significantly increasing the regeneration temperature and rate. Additionally, the oxidation rate was consistent with the kinetic data compiled by Anderson *et al.* (1961). Table 19 presents the rate constant and other data for the catalytic oxidation of methane over alumina supported CuO and CeO₂ taken by Anderson *et al.*

Table 19: Rate Constant and Physical Data for Methane Oxidation Catalysts from Anderson et al. (1961)

Catalyst	% Metal on Support	Support	Catalyst Size (inches)	Frequency Factor (1/s)	Activation Energy (kJ/mole)
Copper Oxide	7.0	γ -alumina	1/8	2.82E5	92.5
Cerium Oxide	1.2	γ -alumina	1/8	3.89E6	120.9

Catalytically reacting methane over the sorbent appears to be a promising method of increasing the reaction rate of methane regeneration. However, additional studies will need to be conducted to determine the long term effects of methane oxidation on the structural and reactive properties of the sorbent.

13.0 Modeling Large Counterflow Moving Bed Regenerators

In a similar manner to the adsorption model, the performance of a bed of sorbent which is being regenerated can be described by an over-all component and material balance on the gas and solid phase, and a set of point rate processes and resistance's containing conservation equations for a single pellet and constitutive equations describing the local rates. The regeneration modeling is simplified in that a counterflow moving bed is somewhat simpler to model than a cross-flow bed, and the surface reaction kinetic resistances dominate any diffusional resistances as seen in Tables 20 through 23.

Table 20: Values for Regeneration Rate Controlling Resistances - CuO/Hydrogen

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	0.37	0.48	0.61
Surface Reaction	$\frac{a_p}{k_r}; a_p = \frac{6(1-\epsilon)}{d_p}$	378	630	1260
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\epsilon)}; \Lambda \approx O(10^3)$	$O(1)$	$O(1)$	$O(1)$
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.14	0.074	0.037
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_K}; k_K = \frac{10D_K}{d_p}$	0.79	0.395	0.20

Table 21: Values for Regeneration Rate Controlling Resistances - CuO/Methane

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	1.20	1.56	2.00
Surface Reaction	$\frac{a_p}{k_r}; a_r = \frac{6(1-\varepsilon)}{d_p}$	2.66E4	5.31E4	1.06E5
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\varepsilon)}; \Lambda \approx O(10^3)$	$O(1)$	$O(1)$	$O(1)$
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.45	0.225	0.11
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_K}; k_K = \frac{10D_K}{d_p}$	2.1	1.05	0.52

Table 22: Values for Regeneration Rate Controlling Resistances - CeO₂/Hydrogen

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	0.87	0.68	0.53
Surface Reaction	$\frac{a_p}{k_r}; a_r = \frac{6(1-\varepsilon)}{d_p}$	58.2	116.5	233.0
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\varepsilon)}; \Lambda \approx O(10^3)$	$O(1)$	$O(1)$	$O(1)$
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.10	0.052	0.026
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_K}; k_K = \frac{10D_K}{d_p}$	0.71	0.35	0.18

Table 23: Values for Regeneration Rate Controlling Resistances - CeO₂/Methane

Controlling Step	Resistance Expression (s/cm)	1/4" Sorbent (s/cm)	1/8" Sorbent (s/cm)	1/16" Sorbent (s/cm)
External Mass Transfer	$\frac{1}{k_f}$	2.10	1.72	1.37
Surface Reaction	$\frac{a_p}{k_r}; a_p = \frac{6(1-\epsilon)}{d_p}$	9142	1.83E4	3.66E4
Internal Diffusion - Solid Phase Diffusion	$\frac{1}{\Lambda k_s}; k_s = \frac{10D_s}{d_p(1-\epsilon)}; \Lambda \approx O(10^3)$	O(1)	O(1)	O(1)
Internal Diffusion - Pore Diffusion	$\frac{1}{k_p}; k_p = \frac{10D_p}{d_p}$	0.35	0.18	0.088
Internal Diffusion - Knudsen Diffusion	$\frac{1}{k_k}; k_k = \frac{10D_k}{d_p}$	2.12	1.06	0.53

The counterflow moving bed performance is determined by solving for the time dependent Me-SO₄ fractional conversion curve using equations (17), (18), and the appropriate point rate expression, and then evaluating the Me-SO₄ fractional conversion at the regenerator outlet by substituting in the sorbent residence time.

14.0 Regenerator Model Input Assumptions

The results of the adsorption model (sulfated sorbent flow rate, sorbent temperature, etc.) are fed directly into the regenerator model. However, several parameters are required as inputs to the regenerator model. A summary of the general input parameters are given in Table 24. Inputs specific to the CeO₂ and CuO sorbents are given in Table 25.

Table 24: General Model Input Parameters

Parameter	Value	Basis
Regenerator Active Height	35 feet	Sorbent flow and mechanical constraints
Adsorber Active Diameter	25 feet	Sorbent flow and mechanical constraints
Reaction Stoichiometry - based on complete metal site regeneration	1.0	No regenerator gas in the effluent gas
Regeneration Efficiency	90 %	Reasonable requirement

Table 25: Sorbent Specific Model Input Parameters

Parameter	Value	Basis
Copper Oxide Sorbent - Hydrogen Regeneration		
Overall Kinetic Rate Constants	$\sim 0.015/s$ at 700 °F	Experimentally Determined - Sorbent Dependent
Heat of Regeneration	5550 Btu/lb-mole CuSO ₄ reacted	Based on heats of formation
Copper Oxide Sorbent - Methane Regeneration		
Overall Kinetic Rate Constants	$\sim 2.0E-4/s$ at 700 °F	Experimentally Determined - Sorbent Dependent
Heat of Methane Oxidation	382,802 Btu/lb-mole CH ₄ reacted	Based on heats of formation
Heat of Regeneration	-62,382 Btu/lb-mole CuSO ₄ reacted	Based on heats of formation
Cerium Oxide Sorbent		
Overall Kinetic Rate Constants	0.0892/s at 1022 °F	Supplied by Hampton University
Heat of Methane Oxidation	382,802 Btu/lb-mole CH ₄ reacted	Based on heats of formation
Heat of Regeneration	-117,656 Btu/lb-mole Ce ₂ (SO ₄) ₃ reacted	Based on heats of formation
Cerium Oxide Sorbent - Methane Regeneration		
Overall Kinetic Rate Constants	5.68E-4/s at 1022 °F	Supplied by Hampton University
Heat of Regeneration	-334,163 Btu/lb-mole Ce ₂ (SO ₄) ₃ reacted	Based on heats of formation

It should be noted that the same words of caution raised concerning the heat of sulfation apply to the heat of regeneration.

15.0 Regeneration Model Results - Required Number of Regenerator Modules

Tables 26 and 27 presents the results of the model for methane and hydrogen regeneration of the CuO and CeO₂ sorbents.

For the copper oxide sorbent, it is anticipated that the regenerator will incorporate the catalytic oxidation of methane to increase the regenerator temperature and decrease the required residence time. The consumption of CH₄ in this process is very small and does not significantly affect the overall CH₄ consumption. The cerium oxide sorbent is not significantly affected by methane oxidation because of the lower reaction rates over cerium oxide. For costing purposes, it is assumed that one regenerator vessel provides

adequate residence time for all processes except the cerium oxide/methane regeneration at 1112 °F, where two vessels are required.

Model output of the fractional sulfate conversion as a function of regenerator residence time is given in Appendix C. This output used the kinetic data of Akyurtlu (1996) (including the heat of reaction, catalytic oxidation of CH_4 - when regenerating with methane, and SO_2 inhibition effects for H_2) in modeling the $\text{Ce}_2(\text{SO}_4)_3$ regeneration, and the kinetic data of Tecogen (1996) (including the heat of reaction and catalytic oxidation of CH_4 - when regenerating with methane) in modeling the CuSO_4 regeneration.

Table 26: Summary of Model Results for Adsorber - Methane Regeneration

Regen. Gas	Regenerator Gas Flow Rate (lb/hr)	Sorbent Flow Rate (lb/hr)	Sorbent Inlet Temp. (°F)	Source of Kinetic Data	Gas/Sorbent Outlet Temperature (°F)	Heat of Reaction Used?	Catalytic Oxidation of CH ₄ ?	SO ₂ Inhibition Effects?	Required Residence Time (min)	Total Number of Vessels
Copper Oxide Sorbents (650 K)										
CH ₄	3702.3	325,844	700	DOE (Yeh <i>et al.</i> 1982)	700	N	N	N	749.6	7
CH ₄	3702.3	325,844	700	Tecogen, 1996	700	N	N	N	1004	9
CH ₄	3702.3	325,844	700	DOE (Yeh <i>et al.</i> 1982)	691.3	Y	N	N	822.9	8
CH ₄	3702.3	325,844	700	Tecogen, 1996	689.5	Y	N	N	1243	11
CH ₄	3702.3	325,844	700	DOE (Yeh <i>et al.</i> 1982)	849.2	Y	Y	N	76.9	1
CH ₄	3702.3	325,844	700	Tecogen, 1996	849.2	Y	Y	N	27.3	1
CH ₄	3702.3	325,844	800	DOE (Markussen <i>et al.</i> 1994)	800	N	N	Y	47.6	1
Cerium Oxide Sorbents (873 K)										
CH ₄	2849.3	553,030	1112	Akyurtlu (1996)	1112	N	N	N	75.5	2
CH ₄	2849.3	553,030	1112	Akyurtlu (1996)	1076	Y	N	N	113.3	2
CH ₄	2849.3	553,030	1112	Akyurtlu (1996)	1078	Y	Y	N	111.8	2
Cerium Oxide Sorbent (923 K)										
CH ₄	2849.3	553,030	1202	Akyurtlu (1996)	1202	N	N	N	28.5	1
CH ₄	2849.3	553,030	1202	Akyurtlu (1996)	1163	Y	N	N	40.5	1
CH ₄	2849.3	553,030	1202	Akyurtlu (1996)	1169	Y	Y	N	40.1	1

Table 27: Summary of Model Results for Adsorber - Hydrogen Regeneration

Regen. Gas	Regenerator Gas Flow Rate (lb/hr)	Sorbent Flow Rate (lb/hr)	Sorbent Inlet Temp. (°F)	Source of Kinetic Data	Gas/Sorbent Outlet Temperature (°F)	Heat of Reaction Used?	Catalytic Oxidation of CH ₄ ?	SO ₂ Inhibition Effects?	Required Residence Time (min)	Total Number of Vessels
Copper Oxide Sorbents (650 K)										
H ₂	1860.7	325,844	700	DOE (Yeh <i>et al.</i> 1982)	700	N	---	N	11.52	1
H ₂	1860.7	325,844	700	Tecogen, 1996	700	N	---	N	6.10	1
H ₂	1860.7	325,844	700	DOE (Yeh <i>et al.</i> 1982)	714	Y	---	N	9.14	1
H ₂	1860.7	325,844	700	Tecogen, 1996	714	Y	---	N	5.40	1
Cerium Oxide Sorbents (823 K)										
H ₂	1074.1	553,030	1022	Akyurtlu (1996)	1022	N	---	N	0.685	1
H ₂	1074.1	553,030	1022	Akyurtlu (1996)	1022	N	---	Y	51.8	1
H ₂	1074.1	553,030	1022	Akyurtlu (1996)	1008	Y	---	N	2.73	1
H ₂	1074.1	553,030	1022	Akyurtlu (1996)	1008	Y	---	Y	60.2	1
Cerium Oxide Sorbent (873 K)										
H ₂	1074.1	553,030	1112	Akyurtlu (1996)	1112	N	---	N	0.264	1
H ₂	1074.1	553,030	1112	Akyurtlu (1996)	1112	N	---	Y	20.0	1
H ₂	1074.1	553,030	1112	Akyurtlu (1996)	1099	Y	---	N	1.03	1
H ₂	1074.1	553,030	1112	Akyurtlu (1996)	1099	Y	---	Y	22.6	1

16.0 Cost Results

Based on the adsorber and regenerator models, preliminary costs can be determined for the reactor vessels and sorbent. Auxiliary FGD equipment has also been estimated based on a 400 MW power plant. The auxiliary equipment includes material handling equipment (bucket elevators, screeners/conveyors, etc.), sulfuric acid plant, storage silos, foundation costs, fly ash handling, and electrical equipment. Economic model assumptions are given in Table 28. Cost summaries for the FGD system are given for cerium to sorbent cost ratios of 1.0, 1.2, and 1.4 and for regeneration with methane and hydrogen in Tables 29-34. All capital costs are uninstalled costs. Results for different regeneration temperatures are not shown because the effect on the overall system cost was negligible.

The cost analysis indicates that the copper oxide system has a lower overall cost of SO_2 removal. This is mainly a result of the ability of the CuO system to operate efficiently at temperatures where carbon steel can be used as the material of construction for the adsorber units. The CeO_2 system operates at temperatures where stainless steels will have to be used, thus increasing the price per adsorber and regenerator module significantly. For methane regeneration, the CeO_2 system has higher O&M costs due to the larger circulation rate, and therefore attrition rate, of the sorbent. For hydrogen regeneration, this cost tends to be offset by the reduced requirement of H_2 regeneration gas which is more expensive than natural gas. It is worth noting that the CeO_2 sorbent may have a larger resistance to attrition, which could decrease the O&M costs well below those for the CuO system.

Table 28: Economic Model Assumptions

Parameter	Assumed Value
Plant Operating Life	30 years
Discount Rate	4.9 %/yr
AFUDC Rate	4.9 %/yr
Hours in year at 100% load	7450 hrs
Levelized Fixed Charge Rate	11.7 %/yr

Table 29: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.0

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	CH ₄	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	CH ₄	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	CH ₄	145	308.8
Cerium Oxide Sorbents (823 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	72	CH ₄	290	1,017
CeO ₂	1/8	38,625	29,000	65	21,616	87	CH ₄	290	1,017
CeO ₂	1/4	41,250	17,679	40	13,262	93	CH ₄	290	1,017
Cerium Oxide Sorbent (873 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	62	CH ₄	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	76	CH ₄	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	81	CH ₄	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mils/kW-hr)	Levelized O&M Charges (mils/kW-hr)	Total Levelized Charges ^{††} (mils/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	198.8	293.3	18.75	543.4	1.81	1.36	3.17
1/8 CuO	20,211	29,406	198.8	293.3	18.75	543.4	1.59	1.36	2.95
1/4 CuO	20,211	26,277	198.8	293.3	18.75	543.4	1.42	1.36	2.78
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,637	153.0	497.7	18.75	669.5	3.11	1.67	4.79
1/8 CeO ₂	20,211	42,931	153.0	497.7	18.75	669.5	2.32	1.67	3.99
1/4 CeO ₂	20,211	34,583	153.0	497.7	18.75	669.5	1.87	1.67	3.54
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,428	153.0	497.7	18.75	669.5	3.05	1.67	4.72
1/8 CeO ₂	20,211	42,066	153.0	497.7	18.75	669.5	2.27	1.67	3.95
1/4 CeO ₂	20,211	33,794	153.0	497.7	18.75	669.5	1.83	1.67	3.50

^{††}Uninstalled Cost

Table 30: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.2

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	CH ₄	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	CH ₄	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	CH ₄	145	308.8
Cerium Oxide Sorbents (823 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	86	CH ₄	145	508.6
CeO ₂	1/8	38,625	29,000	65	21,616	104	CH ₄	145	508.6
CeO ₂	1/4	41,250	17,679	40	13,262	111	CH ₄	145	508.6
Cerium Oxide Sorbent (873 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	74	CH ₄	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	91	CH ₄	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	97	CH ₄	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mils/kW-hr)	Levelized O&M Charges (mils/kW-hr)	Total Levelized Charges ^{††} (mils/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	198.8	293.3	18.75	543.4	1.81	1.36	3.17
1/8 CuO	20,211	29,406	198.8	293.3	18.75	543.4	1.59	1.36	2.95
1/4 CuO	20,211	26,277	198.8	293.3	18.75	543.4	1.42	1.36	2.78
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,652	153.0	597.3	18.75	769.0	3.12	1.92	5.04
1/8 CeO ₂	20,211	42,948	153.0	597.3	18.75	769.0	2.32	1.92	4.24
1/4 CeO ₂	20,211	34,602	153.0	597.3	18.75	769.0	1.87	1.92	3.79
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,440	153.0	597.3	18.75	769.0	3.05	1.92	4.97
1/8 CeO ₂	20,211	42,081	153.0	597.3	18.75	769.0	2.27	1.92	4.20
1/4 CeO ₂	20,211	33,811	153.0	597.3	18.75	769.0	1.83	1.92	3.75

^{††}Uninstalled Cost

Table 31: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.4

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	CH ₄	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	CH ₄	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	CH ₄	145	308.8
Cerium Oxide Sorbents (873 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	100	CH ₄	145	508.6
CeO ₂	1/8	38,625	29,000	65	21,616	121	CH ₄	145	508.6
CeO ₂	1/4	41,250	17,679	40	13,262	130	CH ₄	145	508.6
Cerium Oxide Sorbent (923 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	87	CH ₄	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	106	CH ₄	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	114	CH ₄	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mils/kW-hr)	Levelized O&M Charges (mils/kW-hr)	Total Levelized Charges ^{††} (mils/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	198.8	293.3	18.75	543.4	1.81	1.36	3.17
1/8 CuO	20,211	29,406	198.8	293.3	18.75	543.4	1.59	1.36	2.95
1/4 CuO	20,211	26,277	198.8	293.3	18.75	543.4	1.42	1.36	2.78
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,667	153.0	696.8	18.75	868.6	3.09	2.17	5.29
1/8 CeO ₂	20,211	42,966	153.0	696.8	18.75	868.6	2.29	2.17	4.49
1/4 CeO ₂	20,211	34,620	153.0	696.8	18.75	868.6	1.84	2.17	4.04
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,453	153.0	696.8	18.75	868.6	3.05	2.17	5.22
1/8 CeO ₂	20,211	42,096	153.0	696.8	18.75	868.6	2.27	2.17	4.45
1/4 CeO ₂	20,211	33,827	153.0	696.8	18.75	868.6	1.83	2.17	4.00

^{††}Uninstalled Cost

Table 32: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.0

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	H ₂	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	H ₂	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	H ₂	145	308.8
Cerium Oxide Sorbents (823 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	72	H ₂	145	508.6
CeO ₂	1/8	38,625	29,000	65	21,616	87	H ₂	145	508.6
CeO ₂	1/4	41,250	17,679	40	13,262	93	H ₂	145	508.6
Cerium Oxide Sorbent (873 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	62	H ₂	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	76	H ₂	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	81	H ₂	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mils/kW-hr)	Levelized O&M Charges (mils/kW-hr)	Total Levelized Charges ^{††} (mils/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	1,851	293.3	18.75	2,163	1.81	5.41	7.22
1/8 CuO	20,211	29,406	1,851	293.3	18.75	2,163	1.59	5.41	7.00
1/4 CuO	20,211	26,277	1,851	293.3	18.75	2,163	1.42	5.41	6.83
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,129	1,425	497.7	18.75	1,941	3.09	4.85	7.94
1/8 CeO ₂	20,211	42,422	1,425	497.7	18.75	1,941	2.29	4.85	7.15
1/4 CeO ₂	20,211	34,075	1,425	497.7	18.75	1,941	1.84	4.85	6.69
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,428	1,425	497.7	18.75	1,941	3.05	4.85	7.90
1/8 CeO ₂	20,211	42,066	1,425	497.7	18.75	1,941	2.27	4.85	7.13
1/4 CeO ₂	20,211	33,795	1,425	497.7	18.75	1,941	1.83	4.85	6.68

^{††}Uninstalled Cost

Table 33: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.2

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	H ₂	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	H ₂	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	H ₂	145	308.8
Cerium Oxide Sorbents (823 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	86	H ₂	145	508.6
CeO ₂	1/8	38,625	29,000	65	21,616	104	H ₂	145	508.6
CeO ₂	1/4	41,250	17,679	40	13,262	111	H ₂	145	508.6
Cerium Oxide Sorbent (873 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	74	H ₂	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	91	H ₂	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	97	H ₂	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mills/kW-hr)	Levelized O&M Charges (mills/kW-hr)	Total Levelized Charges ^{††} (mills/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	1,851	293.3	18.75	2,163	1.81	5.41	7.22
1/8 CuO	20,211	29,406	1,851	293.3	18.75	2,163	1.59	5.41	7.00
1/4 CuO	20,211	26,277	1,851	293.3	18.75	2,163	1.42	5.41	6.83
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,143	1,425	597.3	18.75	2,041	3.09	5.10	8.19
1/8 CeO ₂	20,211	42,440	1,425	597.3	18.75	2,041	2.29	5.10	7.40
1/4 CeO ₂	20,211	34,093	1,425	597.3	18.75	2,041	1.84	5.10	6.94
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,441	1,425	597.3	18.75	2,041	3.05	5.10	8.15
1/8 CeO ₂	20,211	42,081	1,425	597.3	18.75	2,041	2.27	5.10	7.38
1/4 CeO ₂	20,211	33,811	1,425	597.3	18.75	2,041	1.83	5.10	6.93

^{††} Uninstalled Cost

Table 34: Cost Summary for CuO and CeO₂ FGD Systems, CuO/CeO₂ Sorbent Cost = 1.4

Metal Oxide	Sorbent Diameter (inches)	Total Adsorber Volume (ft ³)	Total Adsorber Face Area (ft ²)	Number of Adsorber Units	Total Adsorber Cost ^{††} (\$/1000)	Total Sorbent Cost (\$/1000)	Regenerator Gas	Total Regenerator Volume (ft ³)	Total Regenerator Cost ^{††} (\$/1000)
Copper Oxide Sorbents (650 K)									
CuO	1/16	46,667	47,660	106	12,874	105	H ₂	145	308.8
CuO	1/8	75,000	32,143	72	8,717	169	H ₂	145	308.8
CuO	1/4	85,417	20,500	46	5,565	192	H ₂	145	308.8
Cerium Oxide Sorbents (873 K)									
CeO ₂	1/16	31,850	49,000	109	36,337	100	H ₂	145	508.6
CeO ₂	1/8	38,625	29,000	65	21,616	121	H ₂	145	508.6
CeO ₂	1/4	41,250	17,679	40	13,262	130	H ₂	145	508.6
Cerium Oxide Sorbent (923 K)									
CeO ₂	1/16	27,563	48,000	107	35,646	87	H ₂	145	508.6
CeO ₂	1/8	33,606	28,500	64	21,271	106	H ₂	145	508.6
CeO ₂	1/4	36,094	17,500	39	12,994	114	H ₂	145	508.6
Metal Oxide	Auxiliary FGD Cost ^{††} (\$/1000)	Total Capital Costs ^{††} (\$/1000)	Regenerator Gas Cost (\$/hr)	Sorbent Makeup Cost (\$/hr)	Ammonia Cost (\$/hr)	Total O&M Costs (\$/hr)	Levelized Capital Charges ^{††} (mils/kW-hr)	Levelized O&M Charges (mils/kW-hr)	Total Levelized Charges ^{††} (mils/kW-hr)
Copper Oxide Sorbents (650 K)									
1/16 CuO	20,211	33,499	1,851	293.3	18.75	2,163	1.81	5.41	7.22
1/8 CuO	20,211	29,406	1,851	293.3	18.75	2,163	1.59	5.41	7.00
1/4 CuO	20,211	26,277	1,851	293.3	18.75	2,163	1.42	5.41	6.83
Cerium Oxide Sorbents (823 K)									
1/16 CeO ₂	20,211	57,157	1,425	696.8	18.75	2,140	3.09	5.35	8.44
1/8 CeO ₂	20,211	42,458	1,425	696.8	18.75	2,140	2.29	5.35	7.64
1/4 CeO ₂	20,211	34,111	1,425	696.8	18.75	2,140	1.84	5.35	7.19
Cerium Oxide Sorbents (873 K)									
1/16 CeO ₂	20,211	56,453	1,425	696.8	18.75	2,140	3.05	5.35	8.40
1/8 CeO ₂	20,211	42,096	1,425	696.8	18.75	2,140	2.27	5.35	7.63
1/4 CeO ₂	20,211	33,827	1,425	696.8	18.75	2,140	1.83	5.35	7.18

^{††}Uninstalled Cost

17.0 References

- Akyurtlu, A, Hampton University, Private Communication, 1996.
- Anderson, R.B., K.C. Stein, J.J. Feenan, and L.J.E. Hofer, "Catalytic Oxidation of Methane," *Ind. Eng. Chem.*, **53**, pp. 809-812, 1961.
- Bienstock, D. and F.J. Field, "Bench-Scale Investigation on Removing Sulfur Dioxide from Flue Gases," *Journal of the Air Pollution Control Assoc.*, **10**, pp. 121-125, 1960.
- Centi, G., N. Passarini, S. Perathoner, and A. Riva, "Combined DeSOx/DeNOx Reactions on a Copper on Alumina Sorbent-Catalyst. 1. Mechanism of SO₂ Oxidation-Adsorption," *Ind. Eng. Chem. Res.*, **31**, pp. 1947-1955, 1992.
- Centi, G., N. Passarini, S. Perathoner, and A. Riva, "Combined DeSOx/DeNOx Reactions on a Copper on Alumina Sorbent-Catalyst. 2. Kinetics of the DeSOx Reaction," *Ind. Eng. Chem. Res.*, **31**, pp. 1956-1963, 1992.
- Centi, G., A. Riva, N. Passarini, G. Brambilla, B.K. Hodnett, B. Delmon, and M. Ruwet, "Simultaneous Removal of SO₂/NOx from Flue Gases. Sorbent/Catalyst Design and Performances," *Chem. Eng. Sci.*, **45**, pp. 2679-2686, 1990.
- Cho, M.H., and W.K. Lee, "SO₂ Removal by CuO on γ -Alumina," *J. Chem. Eng. Japan*, **16**, pp. 127-131, 1983.
- Davydova, L.P., V.B. Fenelonov, V.A. Sadykov, L.M. Plyasova, and V.F. Anufrienko, "Nature of the Active Component of Applied Copper Oxide Catalysts in Complete-Oxidation Reactions," *Kinetika i Kataliz*, **34**, pp. 99-103, 1993.
- DeBerry, D.W., and K.J. Sladek, "Rates of Reaction of SO₂ with Metal Oxides," *Can. J. Chem. Eng.*, **49**, pp. 781-785, 1971.
- Drummond, C.J., J.T. Yeh, J.I. Joubert, and J.A. Ratafia-Brown, "The Design of a Dry, Regenerative Fluidized-Bed Copper Oxide Process for the Removal of Sulfur Dioxide and Nitrogen Oxides from Coal-Fired Boilers," presented at the 78th Annual Meeting and Exhibition of the Air Pollution Control Association, June, 1985.
- Dixon, J.K., and J.E. Longfield, "Oxidation of Ammonia, Ammonia and Methane, Carbon Monoxide, and Sulfur Dioxide," in *Catalysis*, Ed. P.H. Emmett, Vol. VII, pp. 281-346, 1960.
- Drummond, C.J., J.T. Yeh, J.I. Joubert, J.A. Ratafia-Brown. "The Design of a Dry, Regenerative Fluidized Bed Copper Oxide Process for the Removal of Sulfur Dioxide and Nitrogen Oxides from Coal-Fired Boilers," 78th Annual Meeting and Exhibition of the Air Pollution Control Association, June, 1985.

El-Shobaky, G.A., T. El-Nabarawy, G.A. Fagal, and A.S. Ahmad, "Surface and Catalytic Properties of Copper Oxide Supported on Al_2O_3 and Active Carbon," *Materials Letters*, **17**, pp. 297-302, 1993.

Ergun, S., *Chem. Engr. Progr.*, **48**, p. 89, 1952.

Friedman, R.M., and J.J. Freeman, "Characterization of $\text{Cu}/\text{Al}_2\text{O}_3$ Catalysts," *J. of Catal.*, **55**, pp. 10-28, 1978.

Glass, R.W., and R. A. Ross, "Low Surface Coverage Interactions of Sulfur Dioxide on Selected Transition Metal Catalysts from 273 to 423 K," *Can. J. Chem.*, **49**, pp. 2832-2839, 1971.

Gravelle, P.C., and S.J. Teichner, "Carbon Monoxide Oxidation and Related Reactions on a Highly Divided Nickel Oxide," *Advances in Catalysis*, Ed. D.D. Eley et al., Academic Press, N.Y., **10**, pp. 196-242, 1958.

Hao, Y.G., and B.R. Cooper, "Modeling of Chemisorption on Copper Oxide Supported on Alumina," *Surface Science*, **312**, pp. 250-258, 1994.

Harriot, P. and J.M. Markussen, "Kinetics of Sorbent Regeneration in the Copper Oxide Process for Flue Gas Cleanup," *Ind. Eng. Chem. Res.*, **31**, pp. 373-379, 1992.

Hedges, S.W., and R.A. Diffenbach, "Thermogravimetric Study of Novel Sorbents for Flue Gas Cleanup," presented at the 25th Intersociety Energy Conversion Engineering Conference, Vol. 6, pp. 185-190, 1990.

Hedges, S.W., and J.T. Yeh, "Kinetics of Sulfur Dioxide Uptake on Supported Cerium Oxide Sorbents," presented at the AIChE 1991 Summer National Meeting, Pittsburgh, PA, 1991.

Hedges, S.W., and J.T. Yeh, "Kinetics of Sulfur Dioxide Uptake on Supported Cerium Oxide Sorbents," *Environmental Progress*, **11**, pp. 98-103, 1992.

Hoffman, J.S., D.N. Smith, H.W. Pennline, and J.T. Yeh, "Removal of Pollutants from Flue Gas via Dry, Regenerable Sorbent Processes," presented at the 1992 AIChE Spring National Meeting, 1992.

Kaneko, Y., and H. Odanaka, *J. Res. Inst. Catal. Hokkaido Univ.*, **14**, p. 213, 1966.

Kartheuser, B., B.K. Hodnett, A. Riva, G. Centi, H. Matralis, M. Ruwet, P. Grange, N. Passarini, "Temperature-Programmed Reduction and X-ray Photoelectron Spectroscopy of Copper Oxide on Alumina following Exposure to Sulfur Dioxide and Oxygen," *Ind. Eng. Chem. Res.*, **30**, pp. 2105-2113, 1991.

Kent, S.A., J. Katzer, and W.H. Manogue, "Infrared Spectroscopic Investigation of the Adsorption and Reactions of SO₂ on CuO," *Ind. Eng. Chem. Fund.*, **16**, pp. 443-452, 1977.

Kiel, J.H.A., W. Prins, and W.P.M. van Swaaij, "Performance of Silica-Supported Copper Oxide Sorbents for SO_x/NO_x-Removal from Flue Gas. I. Sulphur Dioxide Absorption and Regeneration Kinetics," *Applied Catalysis B: Environmental*, **1**, pp. 13-39, 1992.

Kiel, J.H.A., and W.P.M. van Swaaij, "A Theoretical Model for the Hydrodynamics of Gas-Solid Trickle Flow Over Regularly Stacked Packings," *AIChE Symp. Ser.*, **85**, No. 270, pp. 11-21, 1989.

Kiel, J.H.A., W. Prins, and W.P.M. van Swaaij, "Modelling of Non-Catalytic Reactions in a Gas-Solid Trickle Flow Reactor: Dry, Regenerative Flue Gas Desulphurisation Using a Silica Supported Copper Oxide Sorbent," *Chem. Eng. Sci.*, **47**, pp. 4271-4286, 1992.

Koballa, T.E., and M.P. Dudukovic, "Sulfur Dioxide Adsorption on Metal Oxides Supported on Alumina," *AIChE Symp. Ser.*, **73**, No. 165, pp. 199-228, 1970.

Krause, A., "Chemisorption, Desorption and Mechanism of Catalytic Reactions on Oxide Catalysts," *Oesterr. Chemiker Ztg.*, **63**, pp. 49-51, 1962.

Lo Jacono, M. and M. Schiavello, "The Influence of Preparation Methods on Structural and Catalytic Properties of Transition Metal Ions Supported on Alumina," in Preparation of Catalysts, Ed. B. Delmon, pp. 473-486, 1976.

Lowell, P.S., K. Schwitzgebel, T.B. Parsons, and K.J. Sladek, "Selection of Metal Oxides for Removing SO₂ from Flue Gas," *Ind. Eng. Chem. Process Des. Develop.*, **10**, pp. 384-390, 1971.

McArdle, J.C., C.P. Luebke and R.B. James, "Kinetic Model Describes SO₂ Adsorption Using a Copper Oxide Sorbent," presented at the Second Annual Coal Conference, Pittsburgh, PA, Sept. 1985.

McArdle, J.C., D.G. Leshock and R.R. Williamson, "Sorbent Life Cycle Testing Fluidized-Bed Copper Oxide Process," presented at the DOE Contractor's Review Conference, Third Annual Coal Utilization and Environmental Control, Pittsburgh, PA, July 1987.

McCrea, D.H., A.J. Forney, and J.G. Myers, "Recovery of Sulfur from Flue Gases Using a Copper Oxide Absorbent," *JAPCA*, **20**, pp. 819-824, 1970.

Markussen, J. and H.W. Pennline, "Investigation of Sorbent Regeneration Kinetics in the Copper Oxide Process," presented at the 1993 SO₂ Control Symposium, August, 1993.

Markussen, J.M., H.W. Pennline, and C.F. Brodd, "A Microbalance Study of the Sorbent Regeneration Kinetics in the Copper Oxide Process," presented at the 1994 AIChE Summer National Meeting, Denver, CO, 1994.

Mars, P., and J.G.H. Maessen, "The Mechanism and the Kinetics of Sulfur Dioxide Oxidation on Catalysts Containing Vanadium and Alkali Oxides," *J. Catalysis*, **10**, pp. 1-12, 1968.

Ostrovskii, Y.V., A.D. Ryabtsev, G.M. Zabortsev, A.A. Shpak, V.V. Popovskii and V.A. Sazonov, "Decrease in Activity of Copper Oxide Catalyst During Prolonged Use," *Zhurnal Prikladnoi Khimii*, **60**, pp. 1470-1474, 1987.

Pennline, H.W., PETC Interim Report, December 1995, CRADA PC-95006.

Pollack, S.S., W.P. Chisholm, R.T. Obermyer, S.W. Hedges, M. Ramanathan, and P.A. Montano, "Properties of Copper/Alumina Sorbents Used for the Removal of Sulfur Dioxide," *Ind. Eng. Chem. Res.*, **27**, pp. 2276-2282, 1988.

Regner, A., and A. Simacek, "Kinetics and Mechanism of SO₂ Oxidation on a Vanadium Catalyst," *Coll. Czech. Chem. Commun.*, **33**, pp. 2540-2547, 1968.

Selwood, P.W., and N.S. Dallas, "Susceptibility Isotherms for Supported Copper Oxide," *J. American. Chem. Soc.*, **70**, pp. 2145-2147, 1948.

Stone, F.S., "Chemisorption and Catalysis on Metallic Oxides," *Advances in Catalysis*, Ed. D.D. Eley et al., Academic Press, N.Y., **13**, pp. 1-54, 1962.

Strohmeier, B.R., D.E. Leyden, R.S. Field, and D.M. Hercules, "Surface Spectroscopic Characterization of Cu/Al₂O₃ Catalysts," *J. of Catal.*, **94**, pp. 514-530, 1985.

Thodos, M., *Chem. Eng. Sci.*, **21**, p. 1191, 1966. As presented in R. H. Perry and C. H. Chilton's Chemical Engineer's Handbook, 5th edition, McGraw Hill: New York, 1973.

Treybal, Mass-Transfer Operations, McGraw-Hill: New York, 1955.

Uysal, B.Z., I. Aksahin, and H. Yucel, "Sorption of SO₂ on Metal Oxides in a Fluidized Bed," *Ind. Eng. Chem. Res.*, **27**, pp. 434-439, 1988.

van der Grift, C.J.G., and J.W. Geus, "Reactions of Silica-Supported Copper Oxide as a Regenerable Sorbent for Flue Gas Desulphurisation," *Thermochimica Acta*, **161**, pp. 131-146, 1990.

Vo Van, K., and F. Habashi, "Kinetics of Reduction of Solid Copper Sulphate by Hydrogen and Carbon Monoxide," *Can. J. Chem. Eng.*, **52**, pp. 369-373, 1974.

Vogel, R.F., B.R. Mitchell, F.E. Massoth, "Reactivity of SO₂ with Supported Metal Oxide-Alumina Sorbents," *Environ. Sci. Tech.*, **8**, pp. 432-436, 1974.

Vorob'ev, V.N., K.K. Shadmanov, Kh.M. Kamilov, and K.Kh. Razikov, "Reduction of CuO-Al₂O₃ Catalysts," *Kinetika i Kataliz*, **27**, pp. 1011-1014, 1986.

Waqif, M. O. Saur, J.C. Lavalley, S. Perathoner, and G. Centi, "Nature and Mechanism of Formation of Sulfate Species on Copper/Alumina Sorbent-Catalysts for SO₂ Removal," *J. Phys. Chem.*, **95**, pp. 4051-4058, 1991.

Winter, E.R.S., "The Reactivity of Oxide Surfaces," *Advances in Catalysis*, Ed. D.D. Eley et al., Academic Press, N.Y., **10**, pp. 196-242, 1958.

Wolberg, A., and J.F. Roth, "Copper Oxide Supported on Alumina. III. X-Ray K-Absorption Edge Studies of the Cu²⁺ Species," *Journal of Catalysis*, **15**, pp. 250-255, 1969.

Yant, W.P. and C.O. Hawk, *J. Am Chem Soc.*, **49**, p. 1454, 1927.

Yates, J.G., and R.J. Best, "Kinetics of the Reaction Between Sulfur Dioxide, Oxygen, and Cupric Oxide in a Tubular, Packed Bed Reactor," *Ind. Eng. Process Des. Dev.*, **15**, pp. 239-243, 1976.

Yeh, J.T. and J.P. Strakey, and J.I. Joubert, "SO₂ Absorption and Regeneration Kinetics Employing Supported Copper Oxide," presented at the 1982 Summer National Meeting of the AIChE, Cleveland, OH, August, 1982.

Yeh, J.T., R.J. Demski, J.P. Strakey, and J.I. Joubert, "PETC Fluidized-Bed Copper Oxide Process for Combined SO₂/NO_x Removal from Flue Gases," presented at the AIChE 1984 Winter National Meeting, Atlanta, GA, 1984.

Yeh, J.T., R.J. Demski, J.P. Strakey, and J.I. Joubert, "Combined SO₂/NO_x Removal from Flue Gas," *Environmental Progress*, **4**, pp. 223-228, 1985.

Yeh, J.T., C.J. Drummond, and J.I. Joubert, "Process Simulation of the Fluidized-Bed Copper Oxide Process Sulfation Reaction," *Environmental Progress*, **6**, pp. 44-50, 1987.

Yoo, K.S., S.D. Kim, and S.B. Park, "Sulfation of Al₂O₃ in Flue Gas Desulfurization by CuO/γ-Al₂O₃ Sorbent," *Ind. Eng. Chem. Res.*, **33**, pp. 1786-1791, 1994.

Appendix A Similarities in Breakthrough Expressions - Adsorption vs. Absorption Modeling

Several investigators have successfully used a first order rate equation based on the reaction mechanism postulated by McCrea *et al.* (1970) to analyze their data (Yeh *et al.*, 1982, 1985, 1987; Kiel *et al.*, 1993; Hedges and Yeh, 1992). McCrea's absorption reaction is

Yeh *et al.* (1982) used this equation to write an expression for the sulfation of the sorbent (rate of consumption of active copper sites):

$$\frac{dY}{dt} = k(1-Y)^n p \quad (\text{A2})$$

This expression is identical to the point rate expression for an irreversible surface reaction dominated adsorption process, and can be solved in a similar manner. However, because the reaction equation used as the basis for the derivation is suspect, one should use Equation (69) with caution. While the form may be correct for reaction limited adsorption, the physics implied by McCrea's expression are quite different and could lead to erroneous conclusions.

McCrea's equation was derived assuming that the CuO is sulfated to bulk CuSO₄, which has not been observed with supported CuO. This becomes clear when the rate constants for the sulfation of bulk unsupported CuO are compared to the rate constants for the sulfation of supported CuO. Table 13 compares the rate constants for unsupported and supported CuO for sorbents which would be reaction rate limited (ground or very small sorbent sizes). Note the large difference in rate constants between the supported and unsupported sorbents.

Table A1: Rate Constants for Supported and Unsupported CuO at 650 K

Investigator	Sorbent Size,	Supported or Unsupported	Rate Constant at 650 K, 1/s
DeBerry and Sladek, (1971)	ground (-170 - 325 mesh)	Unsupported	0.064
Yeh <i>et al.</i> , (1982)	1/16"	γ-alumina supported	0.32
Centi <i>et al.</i> , 1992	0.025" - 0.042"	γ-alumina supported	0.45
Uysal <i>et al.</i> , 1988	0.00738"	γ-alumina supported	0.87

Table A2: Rate Constants for Supported and Unsupported CeO₂ at 823 K

Investigator	Sorbent Size,	Supported or Unsupported	Rate Constant at 650 K, 1/s
DeBerry and Sladek, (1971)	ground (-170 - 325 mesh)	Unsupported	0.064
Yeh <i>et al.</i> , (1982)	1/16"	γ -alumina supported	0.32
Centi <i>et al.</i> , 1992	0.025" - 0.042"	γ -alumina supported	0.45
Uysal <i>et al.</i> , 1988	0.00738"	γ -alumina supported	0.87

The activation energies for supported and unsupported CuO reactions also suggest that the mechanism described by McCrea is not accurate. For unsupported CuO, the activation energy was found to be about 112 kJ/mol (DeBerry and Sladek, 1970), whereas for the supported CuO it is about 20 kJ/mol (Yeh *et al.*, 1982; Centi *et al.*, 1992). For CeO₂, the activation energy is about 33 kJ/mol, whereas it is about between 12 and 17 kJ/mol for supported CeO₂ (Hedges and Yeh, 1992; Akyurtlu, 1996). The larger activation energy for the unsupported metal oxides suggests that the reaction is closer to an absorption reaction, whereas the lower activation energy suggests a weaker SO₂ bond typical of an adsorption reaction.

Another indication that the reaction mechanism of McCrea does not fully describe the sorption process is that it suggests the type of support has little affect on the reaction rate. This has been shown not to be the case by many investigators (Lo Jacono, 1976; Waqif *et al.*, 1991; Friedman and Freeman, 1978; Ostrovskii *et al.*, 1987; Vorob'ev *et al.*, 1986; Strohmeier *et al.*, 1985; Glass and Ross, 1971; Davydova *et al.*, 1993). The substrate significantly changes the structure of the metal ions, as does the metal oxide loading. Supported metal oxides at low loadings form a well-dispersed interaction species with the substrate, and does not form bulk MeO. At higher metal loadings (> 10 percent), bulk MeO begins to appear resulting in a slower reaction rate.

As mentioned above, freshly prepared and used sorbent samples analyzed by X-ray diffraction show neither crystalline MeO or MeAl₂O₄ in the fresh samples nor crystalline Me-SO₄ in the used samples [Centi, (1990, 1992); Friedman *et al.* (1978); Kent *et al.* (1977); Lo Jacono and Schiavello(1976); Pollack *et al.* (1988); Waqif *et al.* (1991), Yoo *et al.* (1994)]. The metal atoms dispersed on the surface of the support materials are not in a well-defined form. This indicates that the sorbents neither start with bulk MeO nor end up with bulk Me-SO₄. Hao and Cooper (1994) suggest that SO₂ is adsorbed on the surface via O-Me bonding and probably to a significant extent in the form of a bridge with the two oxygen atoms of SO₂ sitting at two surface metal atoms. Centi *et al.* (1990), Uysal *et al.* (1988), Waqif *et al.* (1991), Cho and Lee (1983), Lo Jacono (1976) all postulate different, but similar, *adsorption* reactions/bonding.

Finally, investigations into low surface coverage interactions of sulfur dioxide with transition metal catalysts show that the heat of reaction is significantly affected by the substrate and metal loadings. It is generally agreed that sulfur dioxide is adsorbed and reacts with either gas phase oxygen species (Thodos, 1966) or adsorbed oxygen atoms (Kaneko and Odanaka, 1966) or ions (Simicek and Regner, 1968). Variations in heats of adsorption of SO_2 on supported metal oxide catalysts determined by Glass and Ross (1971) support this conclusion.

Appendix B: Adsorber Model Output

1/16" CuO Sorbent Adsorber Outlet Conditions

Fractional Distance from Top (Gas) or Face (Sorbent) of Bed

1/8" CuO Sorbent Adsorber Outlet Conditions

1/4" CuO Sorbent Adsorber Outlet Conditions

1/16" CeO₂ Sorbent Adsorber Outlet Conditions

1/8" CeO₂ Sorbent Adsorber Outlet Conditions

1/4" CeO₂ Sorbent Adsorber Outlet Conditions

Fractional Distance from Top (Gas) or Face (Sorbent) of Bed

1/16" CeO₂ Sorbent Adsorber Outlet Conditions

Fractional Distance from Top (Gas) or Face (Sorbent) of Bed

1/8" CeO₂ Sorbent Adsorber Outlet Conditions

1/4" CeO₂ Sorbent Adsorber Outlet Conditions

Appendix C: Regenerator Model Output

Fractional Copper Sulfate Conversion vs. Regenerator Residence Time

Fractional Copper Sulfate Conversion vs. Regenerator Residence Time

Fractional Cerium Sulfate Conversion vs. Regenerator Residence Time

Fractional Cerium Sulfate Conversion vs. Regenerator Residence Time

Fractional Cerium Sulfate Conversion vs. Regenerator Residence Time

Fractional Cerium Sulfate Conversion vs. Regenerator Residence Time