Phonon Density of States in Fe/Cr (001) Superlattices and Tb-Fe Thin-Film Alloys

W. Sturhahn, R. Roehlsberger, and E.E. Alp
Advanced Photon Source, Argonne National Laboratory, Argonne, IL 60439, USA*

T. Ruckert, H. Schrör, and W. Keune
Angewandte Physik, Universität Duisburg, D-47048 Duisburg, Germany

February 1999

RECEIVED
OCT 13 1999
OSTI

The submitted manuscript has been created by the University of Chicago as Operator of Argonne National Laboratory ("Argonne") under Contract No. W-31-109-ENG-38 with the U.S. Department of Energy. The U.S. Government retains for itself, and others acting on its behalf, a paid-up, nonexclusive, irrevocable worldwide license in said article to reproduce, prepare derivative works, distribute copies to the public, and perform publicly and display publicly, by or on behalf of the Government.

To be published in the proceedings of the International Conference on Magnetic Multilayers, Vancouver, June 15-19, 1998.

*This work is supported by the U.S. Department of Energy, Basic Energy Sciences-Materials Sciences, under contract #W-31-109-ENG-38.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

**PHONON DENSITY OF STATES IN Fe/Cr(001)
SUPERLATTICES AND Tb-Fe THIN-FILM ALLOYS**

W. Sturhahn, R. Roehlsberger, and E.E. Alp
Advanced Photon Source, Argonne National Laboratory, Argonne, IL 60439, USA

T. Ruckert, H. Schrör, and W. Keune
Angewandte Physik, Universität Duisburg, D-47048 Duisburg, Germany

Abstract

Inelastic nuclear scattering of X-rays from the 14.413 keV nuclear resonance of ^{57}Fe was employed to measure directly the Fe-projected phonon density of states (DOS) in MBE-grown Fe/Cr(001) superlattices on MgO(001). The Mössbauer-inactive ^{56}Fe isotope was used in the Fe layers. A 1 Å thick Mössbauer-active ^{57}Fe -probe layer (95% enriched) was placed at different locations within the Fe layers. This procedure permits one to distinguish phonon density of states at the Fe-Cr-interface from that at the center of the Fe-film. Distinct differences have been observed in the DOS of our samples. The phonon DOS of an amorphous $\text{Tb}_{33}\text{Fe}_{67}$ alloy film was found to be a broad and structureless hump, contrary to that of an epitaxial TbFe_2 film, which exhibits characteristic features.

Key words: phonon density of states, inelastic nuclear resonance scattering, Fe/Cr(001) superlattice, Tb-Fe alloy film

complete address, e-mail, telephone and fax of author for correspondence:

W. Keune
Laboratorium für Angewandte Physik
Gerhard-Mercator-Universität Duisburg
D-47048 Duisburg, Germany

Tel: (+49)203-379-2387; Fax: (+49)203-379-3601; Email: keune@uni-duisburg.de

Knowledge of the phonon density of states (DOS) is essential for our basic understanding of lattice vibrations. Extensive investigations of phonons in semiconducting superlattices have revealed novel phenomena, such as folding, confinement and interface modes [1]. For metallic multilayers (MMLs), on the other hand, only few reports of folded [2] or confined [3] phonons exist. Knowledge of vibrational properties of MMLs is highly desirable, also because their electronic properties may be affected by phonons [4]. In the present work inelastic nuclear scattering of X-rays from the 14.413 keV nuclear resonance of ^{57}Fe [5-7] was used to measure directly the Fe-projected phonon DOS in Fe/Cr(001) superlattices and in single films of epitaxial $\text{TbFe}_2(110)$ (Laves phase) and an amorphous $\text{Tb}_{33}\text{Fe}_{67}$ alloy.

Two types of Fe/Cr(001) superlattices (labeled Arg 03 and Arg 04, respectively) were epitaxially grown at 160 °C by MBE on MgO(001) substrates carrying a 50Å Cr buffer layer, which was grown at 670 °C:

Arg 03: $\text{MgO}(001)/\text{Cr}(50\text{\AA})/[^{57}\text{Fe}(0.7\text{ML})/^{56}\text{Fe}(8\text{ML})/\text{Cr}(8\text{ML})]_{200}$

Arg 04: $\text{MgO}(001)/\text{Cr}(50\text{\AA})/[^{56}\text{Fe}(4\text{ML})/^{57}\text{Fe}(0.7\text{ML})/^{56}\text{Fe}(4\text{ML})/\text{Cr}(8\text{ML})]_{200}$

Isotopically depleted ^{56}Fe was used, which gives no nuclear resonance signal. In addition, 0.7 monolayer (ML) thick probe layers of 95.5 % enriched ^{57}Fe were artificially placed either at the ^{56}Fe -on-Cr interfaces (Arg 03) or in the center of the ^{56}Fe layers (Arg 04), thus providing a nuclear resonance signal either from this Fe/Cr interface (Arg 03) or from the Fe-film center (Arg 04). Fig. 1 shows X-ray diffraction (XRD) patterns of Fe/Cr-samples Arg 03 and Arg 04, respectively. The two symmetrical superstructure-statellite peaks demonstrate the high-quality superlattice structure of our Fe/Cr(001) multilayers.

The Tb-Fe alloy films were prepared in UHV by thermal co-evaporation of high-purity Tb

and 95.5 % enriched ^{57}Fe [8]. Films of 175-Å-or 800-Å-thick amorphous (a-) $\text{Tb}_{33}\text{Fe}_{67}$ were grown at 300 K and on Si(001) wafers initially coated with a 200-Å-thick Pt buffer layer. The 800-Å-thick epitaxial $\text{TbFe}_2(110)$ film was grown at 500 °C on a sapphire (11-20) substrate after deposition of a 350-Å-thick Nb(110) buffer layer followed by a thin (15 Å) ^{57}Fe seed layer [9]. The samples were coated with ~ 50 Å Si for protection. XRD patterns of the epitaxial TbFe_2 film and of the a- $\text{Tb}_{33}\text{Fe}_{67}$ (175 Å) film confirmed the $\text{TbFe}_2(110)$ epitaxial orientation and the amorphous structure of this Tb-Fe film, respectively.

The inelastic nuclear resonant absorption experiments were performed at the undulator beamline 3-ID of SRI-CAT at the Advanced Photon Source. Details of the technique are described in ref. [6]. The incident monochromatized synchrotron radiation had an energy bandwidth of 5.5 meV (2.5 meV) in the case of the Tb-Fe alloy films (Fe/Cr superlattices). The energy was tuned around the 14.413 keV nuclear resonance of ^{57}Fe . The measurements were performed at 300 K with collection times of ~ 10 h to ~ 24 h per spectrum.

The measured normalized data (not shown), i.e., the resulting phonon excitation probabilities per unit of energy, commonly feature a dominant elastic peak in a narrow energy range around the nuclear transition energy and side bands at lower and higher energy due to phonon annihilation and phonon creation, respectively [5-7]. The partial phonon DOS were extracted from the measured excitation probabilities by using the procedure described in ref. [6].

The partial vibrational DOS of the 175-Å-thick a- $\text{Tb}_{33}\text{Fe}_{67}$ film (Fig.2) extends up to ~ 40 meV and shows a maximum at ~ 20 meV. It represents a structureless broad feature, as anticipated for such an atomically disordered material. The same result was obtained on an 800-Å-thick a- $\text{Tb}_{33}\text{Fe}_{67}$ film (not shown). By contrast, the partial DOS of the crystalline TbFe_2 film (800 Å) exhibits a sharper maximum at ~ 23 meV and extends to ~ 35 meV. Moreover, a

distinct shoulder appears near 15 meV. Comparison with phonon DOS and dispersion curves for other (bulk) Laves-phase compounds obtained by inelastic neutron scattering [10] shows that the shoulder near 15 meV is related to the high DOS at the Brillouin zone boundary of acoustic modes (longitudinal and transverse), while the main peak near 23 meV is due to optical modes.

The partial phonon DOS of Fe/Cr-samples Arg 03 (interface site) and Arg 04 (center site) show distinct differences (Fig. 3). The DOS of the center site is very similar to that of bulk Fe [6], exhibiting peaks near 23, 28 and 36 meV. Compared to the DOS of the center site (Arg 04), the DOS-peak of the interface site (Arg 03) near 36 meV is remarkably reduced in intensity, while the lower energy feature is notably enhanced. As a possible explanation for the reduction of the 36-meV peak intensity, one should notice that its position nearly coincides with the deep minimum at ~ 34 meV in the bulk-phonon DOS of Cr [10]. Because of this lack of phonon DOS in Cr, part of the Fe phonons near 34 meV remain confined in the Fe layer and are suppressed at the Fe/Cr interface. This confinement affects longitudinal $[00\zeta]$ phonons of Fe near the H point of the Brillouin zone [10].

The work at Argonne is supported by the U.S. Department of Energy BES-Materials Science under Contract No. W-31-109-ENG-38. The work at Duisburg was supported by Deutsche Forschungsgemeinschaft (SFB166). W.K. is grateful to the Volkswagen Stiftung for supporting his stay at Argonne.

- [1] For a review, see B. Jusserand and M. Cardona, in *Topics in Applied Physics: Light Scattering in Solids V*, edited by M. Cardona and G. Güntherodt (Springer, Berlin, 1989), p. 49
- [2] H. Xia, G.X. Cheng, A. Hu, and X.K. Zhang, *Solid State Commun.* 77(1991) 631
- [3] M. Grimsditch, J.E. Mattson, C.H. Sowers, S.D. Bader, and M.J. Peters, *Phys.Rev.Lett.* 77(1996) 2025
- [4] S. Kim, H. Suhl, and I.K. Schuller, *Phys.Rev.Lett.* 78(1997) 322
- [5] M. Seto, Y. Yoda, S. Kikuta, X.W. Zhang, and M. Ando, *Phys. Rev. Lett.* 74 (1995) 3828
- [6] W. Sturhahn, T.S. Toellner, E.E. Alp, X.W. Zhang, A. Ando, Y. Yoda, S. Kikuta, M. Seto, C.W. Kimball, and B. Dabrowski, *Phys. Rev. Lett.* 74 (1995) 3832
- [7] A.I. Chumakov, R. Rüffer, H. Grünsteudel, H.F. Grünsteudel, G. Grübel, J. Metge, and H.A. Goodwin, *Europhys. Lett.* 30(1995) 427
- [8] T. Ruckert, J. Tappert, R.A. Brand, and W. Keune, *J. Magn. Magn. Mater.* 165 (1997) 411
- [9] V. Oderno, C. Dufour, K. Dumesnil, Ph. Mangin, and G. Marchal, *J. Crystal Growth* 165(1996) 175
- [10] W. Kress, *Phonon Dispersion Curves, One-Phonon Densities of States and Impurity Vibrations of Metallic Systems*, Physics Data Vol. 26-1 (Fachinformationszentrum Karlsruhe, Karlsruhe, 1987)

Figure captions

Fig. 1: XRD of Fe/Cr(001)-superlattice sample Arg 03 (top) and Arg 04(bottom). (Cu-K α -radiation)

Fig. 2: Fe-projected phonon DOS of a-Tb₃₃Fe₆₇ alloy film (175 Å) (squares) and of epitaxial TbFe₂(110) film (800 Å) (circles)

Fig. 3: Fe-projected phonon DOS of Fe/Cr(001)-superlattice sample Arg 03 (interface signal) (circles) and Arg 04 (signal from center of Fe layers)(squares).