DOE/PC/94207--T7

M96050224

Quarterly Progress Report

High Temperature Electrochemical Polishing of H₂S

from Coal Gasification Process Streams

Grant DE-FG22-94-PC94207

January 1, 1996 - March 31, 1996

by

Professor Jack Winnick

Georgia Institute of Technology

School of Chemical Engineering

Atlanta, GA 30332-0100

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

W

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

Project Objectives

Coal may be used to generate electrical energy by any of several processes, most of which involve combustion or gasification. Combustion in a coal-fired boiler and power generation using a steam-cycle is the conventional conversion method; however total energy conversion efficiencies for this type of process are only slightly over 30%¹. Integration of a gas-cycle in the process (combined cycle) may increase the total conversion efficiency to 40%¹. Conversion processes based on gasification offer efficiencies above 50%¹.

H₂S is the predominant gaseous contaminant in raw coal gas. Coal depending on the type and area of extraction can contain up to 5 wt% sulfur, which is converted to gaseous H₂S during gasification. Problems arise due to the corrosive nature of H₂S on metal components contained in these cycles. Because of this, H₂S concentrations must be reduced to low levels corresponding to certain power applications. For example, an integrated coal gasification-combined cycle (IGCC) process producing electricity from coal at nearly 50% overall efficiency¹ incorporates gas turbines that cannot tolerate H₂S levels above 100 ppm. Coal gasification/Molten Carbonate Fuel-Cell(MCFC) systems, achieving conversion efficiencies around 60%², function properly only if H₂S is below 1 ppm.

An advanced process for the separation of hydrogen sulfide (H₂S) from coal gasification product streams through an electrochemical membrane is being developed using funds from this grant. H₂S is removed from the syn-gas stream, split into hydrogen, which enriches the exiting syn-gas, and sulfur, which is condensed from an inert sweep gas stream, Figure 1. The process allows removal of H₂S without cooling the gas stream and with negligible pressure loss through the separator. The process is made economically attractive by the lack of need for a Claus process for sulfur recovery. To this extent the project presents a novel concept for improving utilization of coal for more efficient power generation.

Past experiments using this concept dealt with identifying removal of 1-2% H₂S from gases containing only H₂S in N₂³, simulated natural gas^{4,5}, and simulated coal gas⁶. Data

obtained from these experiments resulted in extended studies into electrode kinetics and electrode stability in molten melts^{7,8,9}. The most recent experiments evaluated the polishing application (removal of H₂S below 10 ppm) using the Electrochemical Membrane Separator (EMS). H₂S removal efficiencies over 90% were achieved at these stringent conditions of low H₂S concentrations proving the technologies polishing capabilities.

Other goals include optimization of cell materials capable of improving cell performance. Once cell materials are defined, cell experiments determining maximum removal capabilities and current efficiencies will be conducted.

Also, a model theoretically describing the preferred reduction of H₂S, the transport of S²⁻, and the competing transport of CO₂ will be investigated. The model should identify the maximum current efficiency for H₂S removal, depending on variables such as flow rate, temperature, current application, and the total cell potential.

Introduction

The Electrochemical Membrane Separator (E.M.S.), the focus of experimental work, purges a fuel gas contaminated with H₂S. This is done by reducing the most electro-active species in the gas stream. In this case, H₂S is reduced by the following:

A membrane which contains sulfide ions in a molten salt electrolyte will act to transport the ions across to the anode. If the membrane is impermeable to H₂ diffusion from the cathode side, an inert sweep gas can be used to carry the vaporous oxidized sulfur downstream to be condensed.

Processes to remove H₂S typically rely on low-to -ambient temperature adsorption, followed by sorbent regeneration and Claus plant treatment for conversion of H₂S to a salable by-product, sulfur. Although effective, this type of removal is very process-intensive as well as energy-inefficient due to low temperature operation. Gasification streams generally range from 500°C - 1000°C, requiring cooling before and reheating after process gas sweetening. Although these technologies have proven capable of meeting H₂S levels required by MCFC, there are several disadvantages inherent to these processes^{10,11}.

Alternative high temperature methods are presently available, but process drawbacks including morphological changes in catalytic beds¹² or inefficient molten salt sorbent processes¹³ negate savings incurred through energy efficient removal temperatures.

An electrochemical membrane separation system for removing H₂S from coal gasification product streams is the subject of this investigation. The high operating temperature, flow-through design, and capability of selective H₂S removal and direct production of elemental

sulfur offered by this process provide several advantages over existing and developmental H₂S removal technologies.

Figure 1. Single-Cell View of the Electrochemical Membrane Separator

Quarterly Research

Electrolyte Management

Electrolyte losses associated with molten carbonate salts is a persistent problem. The mechanism of such losses is not fully understood; CO₂ evolution and reactions with cell materials are possible mechanisms.

Proposed mechanisms for the loss of electrolyte in the E.M.S. are:

- 1) Material reactions upon process-gas seal formation:

- 2) Evaporation at the anode due to a deficiency of CO₂:

- 3) Evaporation into the surroundings:

with lithium carbonate, comprising 62 mole% electrolyte, being the least stable (larger K).

Quantitative evaporation studies were performed duplicating full-cell conditions¹⁴. Mechanism (2) & (3) were investigated with evaporation by mechanism (3) entailing the predominant amount of electrolytic losses; 24 hours of exposure evolved on average 30 grams of electrolyte leaving a crystalline residue of Li₂O₂ & Li₂O by:

After extended real-time experimentation utilizing stainless steel as housing materials, electrolyte diffusion into the housings apparently occurred. This was evidenced during post-mortem analysis; the housings were heated to ~650°C in order to burn-off excess volatiles used for surface sterilization. After thermal cycling crystals appeared on the housing surface; approximately 1.5 grams of the material was recovered for analysis by crystallographic

techniques. X-ray diffraction revealed that the crystals were almost pure lithium carbonate Figure 2. One would expect that potassium carbonate would be apparent as well, in a ratio similar to the molar composition of the electrolyte (62 mole% lithium, 38 mole% potassium).

Mechanism (2) would give a suitable explanation for this phenomenon since diffusion of Li_2O would occur more readily than Li_2CO_3 based on molecular size. This also explains preferential diffusion of lithium species compared to potassium species by comparison of equilibrium constants; dissolution of lithium carbonate is a factor of 10 higher than potassium carbonate.

The conclusion drawn from these findings accentuates the necessity for sealing the electrolyte/housing interface with an electrically as well as chemically inert material of minimum porosity. Continued use of alumina should provide the adequate substrate if the proper technique can be found for inducing a thin, non-porous layer on the stainless steel surface.

Sturdy seals were obtained recently by coupling aluminum foil gaskets with aluminum paint(29 wt%) to increase adherence to the housing surface.

Figure 2. X-ray Diffraction of Crystal Growth on Stainless Steel Housings

Cathode Materials

From results obtained in previous studies, the path to a commercial process is now clear. The primary unresolved components are the cathode and membrane. The cathode must be chemically and mechanically stable in the sulfide/carbonate/hydrogen sulfide environment, and be electronically conductive at 650°C. Lithium-doped NiO has already proven effective in polishing applications; however, the Ni phase transition to liquid $\text{Ni}_{3+x}\text{S}_2$ when contacting gas with >100 ppm H_2S , requires alternate cathode materials. Co, which converts to Co_8S_9 in-situ, has recently been shown¹⁵, using Scanning Electron Microscopy (S.E.M.), to be morphologically stable in full cell testing with 100 ppm H_2S . The microscopic view revealed adequate porosity and pore size were maintained in the harsh cell environment. Production of cobalt electrodes in the laboratory is ongoing; consistently manufacturing these electrodes with a pore size and arrangement comparable to the Ni electrodes has been accomplished although current attempts have been less successful. Dry pressing the cobalt powder ($d_p = 2$ microns) with ~ 40 wt% binder (methylethylcellulose) stabilized the metal in disk form to accomplish the burnout and sintering steps. Stress fractures often occur due to the non-uniform release of binder and apparent temperature inequality within the furnace. These concerns involve the physical aspects of dry pressed powders. Non-uniform distribution of binder material incorporated within the cobalt particles creates particle segregation in certain regions; local density gradients due to disproportionate binder distribution effects the final electrode morphology (i.e. pore size, pore distribution, tortuosity, and crystallographic stability). Adjustments dealing with binder content and temperature cycling will be the impetus of future membrane production as well as improvements in dry-pressing of the cobalt-binder system.

Eventual scale-up of the E.M.S. system must incorporate cobalt electrodes; bench-scale experiments have confirmed that consistent inlet H_2S levels are difficult to control. This would be detrimental in a full-scale operation where a high local H_2S density could result in electrode destruction.

Another alternative would allow use of Ni as the cathode material but require a lower run temperature (~580 C) to avoid the liquid NiSy from forming²¹.

Membrane Materials

Several membranes have been utilized in the EMS since its genesis. MCFC tiles used by Weaver¹⁶, sulfided in-situ, resulted in micro-crack development; however MCFC tile technology will be used in scale-up applications of electrochemical separations, due to success in real-time MCFC. The technology has been refined, but replication in our laboratory is expensive and inefficient for bench-scale testing. Tape-cast membranes of MgO were somewhat more efficient but inconsistent laboratory replication proved detrimental¹⁷; however, tape casting with zirconia particles still remains a viable option. The most promising membranes for bench-scale experiments have been manufactured zirconia membranes purchased from Zircar Corporation. Polishing of the gasification streams with these membranes confirms their usefulness; however micro-cracks are still evident from S.E.M. analysis¹⁵, Figure 3, and must be controlled. Alternative laboratory-densified membranes with fiber mats replicating the preprocessed membranes from Zircar Corporation are also being investigated. Positive removal results (over 90% H₂S removal) have been obtained from full-cell testing with these membranes¹⁸; however, more work is needed to improve the manufacturing techniques. Dry pressing zirconia particles admixed with binder has been the most recent attempt to produce a viable membrane material as well as tape-casting sub-micron ZrO₂ particles in a solvent-binder system. Run 24 & 25 this quarter utilized a fabricated membrane and a tape-cast membrane respectively, which provided a consistent ionic pathway between electrodes as well as segregating process gases from sweep gases.

Zirconia Cloth-Stabilized Matrices

Continued cell testing will be done utilizing the purchased zirconia membranes along with laboratory-densified zirconia membranes containing zirconia fibers. Laboratory-densified

membranes which have proven successful in the past ¹⁸ will be tested further. One reason for this is financial. Conventional purchased zirconia membranes cost approximately \$ 150.00 per membrane (7.62 cm (3 in) x 7.62 cm (3 in) x 0.063 cm (0.025 in)), compared to \$ 10.00 per membrane (7.62 cm (3 in) x 7.62 cm (3 in) x 0.092 cm (0.036 in)) for self-produced membranes.

Figure 3. S.E.M. View of a Purchased Zirconia Membrane

Laboratory-densified membranes consist of two knit zirconia mats (7.62 cm (3 in) x 7.62 cm (3 in) x 0.0762 cm (0.030 in)) purchased from Zircar Corporation. The initial porosity of the mats is approximately 85%. The objective is to fill (rigidize) the knit to a porosity of approximately 65%, which is essential, according to past experiments, in order to operate efficiently¹⁹. The material used to rigidize the membrane is an aqueous suspension of sub-micron zirconia particles. The combination of mats are submerged in a container of rigidizer,

then placed under a vacuum to evacuate the pores. Once pores are relieved of gaseous fillers, the rigidizer infiltrates the pores.

In previous manufacturing, after the infiltration step, the membrane(cloth plus aqueous suspension of sub-micron zirconia particles) was placed on a flat Teflon surface, covered with weighing paper, and constrained from curling by a metal mesh. More recent techniques relied on the wet matrices being placed atop a thin wire bent into a square configuration and attached to a speed controlled rotor; the rotating of the free body should allow a faster more uniformly dry body(matrices) compared to previous techniques.

Once dry, the membrane is analyzed for void fraction and reprocessed if found unacceptable. In the cell, the 65% porous membrane with infiltrated electrolyte prevents cross-over of harmful amounts of hydrogen and allows a low-resistance path for sulfide diffusion and migration. In order to reach such porosity, the method of rigidization must be performed several times, each reducing the porosity by approximately 10%. Every cycle requires drying, placing mechanical stress on the membrane. The fabricated membrane meeting the 65 % porosity performed adequately in full- cell testing¹⁸.

Thus far improvements in laboratory-densified manufacturing techniques consist of: i) Adding zirconia rigidizer into a knit-zirconia matrix under an extended vacuum (>5 min.). This drastically decreases porosity , reducing the number of steps required to fabricate the membrane. ii) Suspending the mat during drying to increase diffusion since both faces of the mat are exposed, decreasing solvent diffusion distance and iii) vertically rotating the suspended body to uniformly distribute the suspension of zirconia particles throughout the membrane.

Preliminary manufacturing using the rotary dryer failed due to handling problems; Figure 4 reveals an S.E.M. view of membrane cracks connected to these problems. Improvements in the process between steps i and ii are being handled with a more efficient rotor frame, stabilizing the cloth mat prior to the infiltration of the zirconia particles therefore creating a more desirable transition from the vacuum chamber to the rotary drying stage. Processing of membranes with this technique will continue.

Figure 4. S.E.M. View of a Self-Fabricated Zirconia-Cloth Membrane

Dry Pressing

Dry pressing of sub-micron zirconia particles with a percentage of binding material corresponding to a desired porosity has been attempted. Stages in dry pressing include i) the filling of a circular 3 inch diameter carbon steel die with the zirconia particle binder mixture, ii) compacting and shaping of the zirconia binder admixture, and iii) ejection of the pressed disk. Pressing can be accomplished by uni-axial pressing Figure 5a or isostatic pressing Figure 5b. Uni-axial pressing was the technique of choice for initial compression experiments due to ease and availability.

In dry-pressing , pressure produced by moving the die punches compacts the zirconia-binder powder mixture into a cohesive disk with a certain shape and micro-structure according to

the extent of applied pressure and binder content. Generally pressures range from 10 - 200 MPa although above 10 MPa rate of densification decreases rapidly; binder content is between 2 and 12 vol% ²⁰. Dry-pressing of the zirconia-methocel system was accomplished with a pressure of 20 MPa and a binder content of ~ 50 vol%. A high membrane porosity necessitates a higher than normal binder content although inherent problems in binder burnout are inevitable.

Figure 5 Dry-Pressing with an a) Isostatic Stress Loading and b) Uni-axial Stress Loading

Initial attempts at membrane manufacture by dry-pressing showed promise. Figure 6, an S.E.M. view of the sintered dry-pressed zirconia membrane, reveals an acceptable membrane surface and pore distribution; membrane porosity was ~ 60 % with an average pore size of 1 micron. Work must continue on obtaining a more uniform membrane surface creating parallelism between membrane, electrode, and housing materials as well as alleviating stress fractures during binder burnout and sintering which can lead to cracks. Also reduction in membrane thickness must be addressed in order for the dry-pressed membranes to be a viable options for E.M.S. bench-scale experiments; three experiments yielded a membrane of thickness ~ 0.2 cm. Previous membranes utilized successfully in the E.M.S. removal system had a thickness of ~ 0.5 mm.

Figure 6. S.E.M view of a Dry-Pressed Membrane

Tape casting

Tape casting is the process of forming a film of controlled thickness under a blade onto a supported substrate. Tape-casting provides a smooth membrane surface as well as a thin (0.01 - 1 mm), flat, uniform, and somewhat compressible membrane²⁰. Membranes produced by dry-pressing and extrusion have a less smooth surface below 2 mm in thickness, consist of breakage, non-uniform density, and a non-parallelism between surfaces can be a problem; therefore tape cast membranes if manufactured properly could produce viable membranes for the E.M.S. system, shown in Figure 7. Tape-cast membrane stability throughout the duration of run 25 shows strong support for continued casting efforts.

Tape-casting can be performed continuously or as a batch process. Industrial applications utilize the high volume capacity from continuous casting for multilayer ceramic electronic packaging, multilayer capacitors, piezoelectric devices, thick and thin film insulators, and catalyst supports²⁰. Low volume bench-scale requirements (i.e. electrochemical matrices) are ideal for batch production. Examples of batch components used industrially and on our bench-scale membranes are given in Table I and II respectively.

Figure 7. S.E.M. of Tape-Cast Membrane for Bench-scale Experimentation

Table I. Examples of Compositions of Tape-Casting Slurries²⁰ (Industrial)

Component	Alumina Tape	Comp. (vol%)	Titanate tape	Comp. (vol%)
Ceramic powder	Alumina powder*	27	Titanate powder*	28
Liquid system	Trichlorethylene	42	Methylethyl ketone	33
	Ethanol	16	Ethanol	16
Deflocculant dispersant	Menhaden fish oil	1.8	Menhaden fish oil	1.7
Binder	Polyvinyl butyral	4.4	Acrylic	6.7
Plasticizer	Polyethylene glycol	4.8	Polyethylene glycol	6.7
	Octyl phthalate	4.0	Butyl benzyl phthalate	6.7
Surfactant			Cyclohexanone	1.2

* < 5 μ m, includes sintering aids, grain growth inhibitor

Table II. Example of Composition of Tape-Casting Slurry (Bench-Scale)

Component	Zirconia Tape	Comp. (vol%)
Ceramic powder	Zirconia powder*	16.3
Liquid system	Toluene	47.9
	Denatured Ethyl alcohol	13.2
Deflocculant dispersant	M-111X	4.5
Binder	Vinyl	8.9*
Plasticizer	Unknown	4.6*
Surfactant	Unknown	4.6*

* compositions are a best guess from characteristic values given by metoramic sciences, inc., see Table IV

Borosilicate membranes

Alternate matrix materials also have been investigated including microporous glass membranes with porosities of 0.2 and 0.02 microns, shown in Figure 8 and a thickness of 60 microns exceeding the probable limit of the bench-scale E.M.S. set-up provisions; thus far, these membranes have shown chemical instabilities with the electrolytic melt. Several experiments to illuminate the chemical stability of these membranes in the molten salt electrolytic melt showed

a trend of membrane dissolution throughout the melt. Without a stable matrices to entrain the electrolyte, leakage will occur reducing the ionic pathway between electrodes which is detrimental to E.M.S. performance. Future tests with these membranes are not scheduled.

Sol-Gel membranes

Testing commenced with SiO_2 Sol-Gel membranes with an engineered pore structure. Chemical testing proved detrimental to the membrane morphology similar to the boro-silicate membranes. The mechanism for SiO_2 dissolution is unknown. Future chemical testing should provide evidence of Sol-Gel membrane usefulness for real-time experiments. An advantage of these membranes involves the ability to manipulated pore structure providing a better ionic pathway as well as electrolytic distribution throughout system components.

Figure 8. S.E.M. View of a Borosilicate Membrane

Membrane Thickness

Once effective membranes have been developed, other variables such as thickness of the membrane will be investigated in high-flow rate experiments in order to lower the resistance to sulfide migration. The rate of mass transport corresponding to sulfide migration through the membrane is given by:

$$i = \frac{nFD (C_c - C_a)}{\delta} \quad (3)$$

where n is the charge number, F is Faraday's constant, D is diffusion coefficient, δ is the membrane thickness, and C is the concentration of sulfide species at the cathode and anode. At high process-gas flow rates, mass transfer from the gas is equivalent to the limit of diffusion through the membrane, given by:

$$i_l = \frac{nFD C_c}{\delta} \quad (4)$$

The limiting current is a measure of the maximum rate at which sulfide can be transported through the membrane, and occurs when $C_a = 0$. Equation (4) reveals that a thinner membrane creates a higher limiting current for the transport of sulfide. This is extremely important at high flow rates to insure diffusion from the bulk process-gas is the only limiting factor.

Optimization of membrane thickness and porosity will be investigated at high flow rates during full-cell testing using a singular laboratory-densified membrane, thickness ~ 0.38 mm (0.015 in) as well as tape cast and dry-pressed membranes discussed earlier.

Quarterly Summary

Cathode manufacturing coupled with full-cell experimentation was the primary focus this quarter. A tape-casted cobalt cathode was developed and utilized in three full-cell experiments (run 26, run 27, and run 28); tape-cast zirconia membranes were used in run 26 and run 27, while run 28 utilized a fabricated membrane purchased from Zircar Corporation. Table III gives an outline of the membrane materials as well as other components used for experiments 26, 27, and 28.

Three full-cell experiments served a three-fold purpose: 1) testing the electrochemical membrane separators ability to concentrate CO_2 ; 2) testing the electrochemical membrane separators ability to remove H_2S ; and 3) testing modifications of the experimental apparatus(i.e. tape-cast cobalt electrodes).

Table III. Experimental Components

Run	Temp. °C	Cathode	Anode	Membrane	Housings	Electrolyte
26	650	Tape-cast Co	Lithiated NiO	Tape-cast (ZrO ₂)	Stainless Steel (316)	(Li _{0.62} K _{0.38}) ₂ CO ₃
27	650	Tape-cast Co	Lithiated NiO	Tape-cast (ZrO ₂)	Stainless Steel (316)	(Li _{0.62} K _{0.38}) ₂ CO ₃
28	650	Tape-cast Co	Ni	Fabricated (ZrO ₂)	Stainless Steel (316)	(Li _{0.62} K _{0.38}) ₂ CO ₃

Run #26

Five ZrO₂ tape-cast membranes were combined for use in the E.M.S. system. The slurry to produce these membranes in a batch-wise process consisted of 10 grams ZrO₂ powder ($d_p \sim 0.2 \mu\text{m}$) mixed with 7.41 grams of a binder-solvent system (B-73305, characteristics of which are

given in Table IV), coupled with 0.1 grams of surfactant/dispersant (M-1114). Mixture of the ceramic, binder-solvent system is based on the desired membrane characteristics; optimal porosity is in the 50 to 70% range with pore diameters of 0.1 microns. The ceramic loading into the binder-solvent system necessary for obtaining a ceramic matrices of 50% porosity is calculated as follows:

$$\text{Grams of B73305} = \left(\frac{\text{grams of ZrO}_2}{\text{density of ZrO}_2 \left(\frac{\text{grams}}{\text{cm}^3} \right)} \right) \times \left(\frac{\text{density of binder solids} \left(\frac{\text{grams}}{\text{cm}^3} \right)}{\text{wt\% binder solids} \left(\frac{\text{grams of binder solids}}{\text{grams total}} \right)} \right) \quad (5)$$

Table IV. Characteristics of the Metoramic Science Binder-Solvent System B-73305

Resin Type	Vinyl
Typical Composition (wt%)	61.3 Toluene 15.3 Denatured ethyl alcohol 23.4 Other additives: polymer, surfactants, plasticizers, adhesion, and porosity modifiers
Typical Properties	Binder solids 22.3 wt% Binder Viscosity 550 cps Binder Specific Gravity 0.88 Binder Solids Specific Gravity 1.0 Wt per Gallon 7.33 lbs. (3.33 kg)
Appearance	Clear to slightly hazy-yellow solution

Five membranes of 50% porosity were successfully manufactured in a batch-wise process. The dimensions of each membrane are as follows in Table V:

Table V. Tape-cast Membrane Dimensions

Membrane	Weight (grams)	Area (cm x cm)	Thickness (mm)
1	1.217	5.08 x 5.08	0.25
2	1.264	5.08 x 5.08	0.25
3	1.184	5.08 x 5.08	0.23
4	1.190	5.08 x 5.08	0.23
5	0.860	~5.08 x 5.08	0.20

The 3.41 grams of electrolyte needed to saturate the combination of ceramic membranes was inserted in-situ after process components reached run temperature (650 C).

A novel tape-cast cobalt cathode was used in run 26. Characteristics of the cast were similar to the tape-cast zirconia membrane. The higher density cobalt, compared to zirconia, decreased the required binder-solvent material, B73305 (5.04 grams), for a 50% porous material. Table VI gives a compilation of electrode dimensions developed from the tape-cast.

Table VI. Tape-cast Electrode Dimensions

Membrane	Weight (grams)	Diameter (cm)	Thickness (mm)
1	0.818	3	0.39
2	0.848	3	0.39
3	0.891	3	0.39
4	1.000	3	0.43
5	0.738	3	0.36

Since Co was used as a cathode material H_2S levels over 50 ppmv could be applied to the cell; the phase transition previously evidenced from solid-conductive NiO to the molten-conductive $\text{Ni}_{3+x}\text{S}_2$ could be avoided. Housing materials consisted of 316 stainless steel with two pressed aluminum disk as process-gas sealants; adherence of process seals to the housings was aided by application of aluminum paint(29 wt% Al). An 85% porous Ni anode was obtained from Energy Research Corporation.

Upon full-cell start-up the initial temperature was set at 150 °C. Binder-burnout was evidenced by smoke and organics in the exhaust. Cathode and anode gas flow rates were 50 cc/min N_2 and 45 cc/min N_2 respectively. Temperature was increased in 10 °C intervals, starting from 150 °C, as binder volatiles dissipated. Binder volatiles were not apparent after holding the temperature at ~ 450 C (just below the electrolytic melting point of 490 C) for more than 12 hours.

Continued heating element failure caused shut-down after 75 hours; corrections to system components ensued.

Run #27

Four ZrO_2 tape-cast membranes were combined for use in run 27. The slurry to produce these membranes in a batch-wise process consisted of 10 grams ZrO_2 powder ($d_p \sim 0.2 \mu\text{m}$) mixed with 6.64 grams of a binder-solvent system (k-565, characteristics of which are given in Table VII), coupled with 0.2 grams of surfactant/dispersant (M-1114 & M-1111). Mixture of the ceramic, binder-solvent system is based on the desired membrane characteristics; optimal porosity is in the 50 to 70% range with pore diameters of 0.1 microns. The ceramic loading into the binder-solvent system necessary for obtaining a ceramic matrices of 50% porosity is calculated as follows:

$$\text{Grams of K565} = \left(\frac{\text{grams of ZrO}_2}{\text{density of ZrO}_2 \left(\frac{\text{grams}}{\text{cm}^3} \right)} \right) \times \left(\frac{\text{density of binder solids} \left(\frac{\text{grams}}{\text{cm}^3} \right)}{\text{wt\% binder solids} \left(\frac{\text{grams of binder solids}}{\text{grams total}} \right)} \right) \quad (6)$$

Table VII. Characteristics of the Metoramic Science Binder-Solvent System K565

Resin Type	Acrylic
Typical Composition (wt%)	37 - Isopropylalcohol 37 - Heptane 26 - Other additives: polymer, surfactants, plasticizers, adhesion, and porosity modifiers
Typical Properties	Binder solids 24.89 wt% Binder Viscosity 100 cps Binder Specific Gravity 0.79 Binder Solids Specific Gravity 1.0
Appearance	Pale yellow liquid

Four membranes of 50% porosity were successfully manufactured in a batch-wise process. The dimensions of each membrane are as follows in Table VIII:

Table VIII. Tape-cast Membrane Dimensions

Membrane	Weight (grams)	Area (cm x cm)	Thickness (mm)
1	1.362	5.08 x 5.08	0.29
2	1.458	5.08 x 5.08	0.30
3	1.440	5.08 x 5.08	0.29
4	1.339	5.08 x 5.08	0.30

The 3.0 grams of electrolyte needed to saturate the combination of ceramic membranes were introduced into the cell after cell temperature reached 650 C.

Tape-cast cobalt electrodes, dimensions of which are shown in Table IX, were again produced in order to alleviate electrode morphology damage in a high H₂S environment.

Table IX. Tape-cast Electrode Dimensions

Membrane	Weight (grams)	Diameter (cm)	Thickness (mm)
1	0.818	3	0.39
2	0.848	3	0.39
3	0.891	3	0.39
4	1.000	3	0.43
5	0.738	3	0.36

Initially, nitrogen flow to both sides of the cell aided in transporting membrane and cathode volatiles at burn-out temperature (~380 C). After completion of binder burnout, temperature was increased to 650 C, where introduction of electrolyte occurred. Evaluation of system performance was accomplished by addition of fuel gas to the cathode side of the cell (flow rate = 169 cc/min), CO₂ to the anode side of the cell (flow rate = 172 cc/min), and application of current; CO₂ removal from the cathode side was less than stoichiometric and production on the anode side revealed similar inefficiency. Introduction of H₂S (~3000 ppmv) to

the cell ensued although system permanence was never established through CO_3^{2-} transport. Stoichiometric current required to remove 90% of inlet H_2S failed to effect outlet levels; continual current ramping had a negligible effect. Internal resistance remained surprisingly low, $\sim 0.2 \Omega$, indicative of a possible short between the cathode and anode side of the E.M.S. system. Eventual shut-down occurred after 99 hours, due to a short created by an aluminum bridge between housing materials.

Run #28

A fabricated zirconia membrane was utilized in run 28. Housings were stainless steel(316). Electrodes consisted of a tape-cast cobalt cathode and a nickel anode(purchased from Energy Research Corporation).

Upon full-cell start-up the initial temperature was set at 200 C and increased to 650 C in 50 C increments. Cathode and anode gas flow rates were 150 cc/min N_2 and 100 cc/min N_2 respectively. Once the cell temperature reached 650 C, 2.0 grams of electrolyte were added; cathodic flow was adjusted to 175 cc/min; 60 cc/min was comprised of fuel gas (6% CO_2 , 18% CO , and 13% H_2) and the remaining 115 cc/min of N_2 . The anodic inlet gas consisted of 127 cc/min N_2 , 9 cc/min CO_2 .

Evaluation of theoretical CO_2 removal from the process-gas (cathode-gas) with applied current was the first test conducted on the Electrochemical Membrane Separator (E.M.S.) full-cell run; percentage of CO_2 removal at the cathode and corresponding production at the anode compared to the theoretical values determines system permanence. Application of 100 mA to the cell caused process-gas CO_2 levels to increase by $\sim 50\%$ of the theoretical value at the anode, however CO_2 removal at the cathode was negligible. 100% of the theoretical value is necessary before H_2S application. Internal resistance was 1Ω which is an acceptable value. Cell process-gas seals developed sporadically causing problems with removal analysis. Excessive electrolyte required to maintain appropriate gas seals eventually saturated the anode and clogged the anode gas outlet tube.

Shut-down of run 28 eventually occurred after 9 hours of operation due to several.

Conclusion

The Fossil Energy Advanced Research Program requires high temperature separations to remove environmental contaminants from post-combustion flue gases as well as pre-combustion process gases. This project is aimed at the latter: the removal of hydrogen sulfide from coal gas at gasifier temperatures. This development would enable a simplification of the entire gasification scheme by permitting a one-step removal of hydrogen sulfide and production of elemental sulfur. Energy savings accrue due to the high temperature processing.

The DOE programs relating to gasification for power production have as their goal the more efficient, clean paths toward affordable energy from coal. Gas clean-up accounts for nearly one-third of the cost of this conversion. Simplification and economization will benefit the entire effort.

Project Output

Current experiments are based on improving selective removal from low initial H₂S concentrations (100 ppm and 20 ppm H₂S). High flow rate effects, membrane stability and selectivity, and electrode morphology characterizes present studies, with recent results showing over 90% H₂S removal with applied current.

Experimental results presented are based on two experiments with initial H₂S concentrations of 100 ppm and 20 ppm. To represent probable industrial conditions, variables such as flow rates, selectivity of the membranes, and process-gas seals, were of primary concern in these experiments. Maximum removals of H₂S are reported on a zero current basis, thus compensating for any chemical scrubbing effects of the non-equilibrium electrolyte species in the membrane. Percent H₂S removal with applied current exceeded 80% and in some cases reached 90%, given by:

$$\%H_2S \text{ Removal} = \frac{(\text{Outlet } H_2S_{\text{zero current}} - \text{Outlet } H_2S_{I_{\text{applied}}})}{(\text{Outlet } H_2S_{\text{zero current}})} \times 100 \quad (7)$$

Cell housing materials used for both experiments were a machineable ceramic (MACOR). Cathode and anode electrodes consisted of Ni, oxidized in situ to form NiO. Process-gas seals developed, in-situ, by placing aluminum foil gaskets on both sides of the electrolyte filled membrane. Al oxidation initially forms Al_2O_3 which on reaction with Li, contained in the electrolyte, forms $LiAlO_2$.

The membrane for the 100 ppm experiment, used two tapes of MgO and one mat of zirconia cloth. Acrylic binders used in the MgO tapes (Metoramics K565-4 binder system) were burned out under an O_2 atmosphere at $350^\circ C$ and the $(Li_{0.62}K_{0.38})_2CO_3$ eutectic-composition electrolyte was added with the cell at run temperature. Inlet gases were passed through a stainless steel shift reactor, allowing them to equilibrate before passing through the cell. Gas compositions at 973K after the shift reactor were 14.3% CO_2 , 50.8% CO , 4.8% H_2O , 30.1% H_2 , and 100 ppm H_2S .

H_2S removal vs. applied current, with a cathodic flow rate of 88 cc/min., is presented in Figure 19. H_2S removals of 90% were achieved with H_2S current efficiencies of 5%.

The membrane for 20 ppm experiments was purchased from Zircar Corporation, consisting of yttria-stabilized zirconia in a rigid form at 66% porosity. The advantages of these membranes are consistently uniform porosities and no warping. A cold pressed disk of the Li/K eutectic carbonate electrolyte, placed between the cathode housing and the Zircar membrane, provided a stable start-up configuration. Inlet gases equilibrated to 5.8% CO_2 , 25.6% CO , 6.7% H_2O , and 65.3% H_2 , after the water-gas shift reactor. The electrolyte sulfide concentration equilibrated in-situ to 0.11 mole%.

Temperature remained constant (650°C) while flow rates varied from 170 cc/min. to 814 cc/min. H_2S removal at all flow rates exceeded 80% with applied current as shown in Figure 20; Current efficiencies were $\sim 35\%$.

Figure 9. H_2S Current and Removal Efficiency vs. Current Density; 100 ppm inlet H_2S

Cathodic Flow Rate = 88 cc/min

Figure 10. H₂S Current and Removal Efficiency vs. Current Density; 20 ppm inlet H₂S

Parametric values are in cc/min

Future Goals

A continual problem with the E.M.S. system is an appropriate cathode material with chemical and electrochemical stability in the high temperature corrosive environment. At high levels of H_2S , the Ni cathode converts to a molten NiS_y creating adverse effects mentioned previously. A review of the literature²¹ revealed that maintaining a temperature below 635 C, usual experiments are performed at 650 C, prevents the liquid NiS_y from forming. Next quarters experiments will be performed at 580 C with the E.R.C. Ni electrodes at the anode and the cathode. Co electrodes will continue to be investigated as well; however, persistent oxidation of the material during binder-burn-out has created adverse reactions schemes upon applications of current exposing permanent damage to E.M.S. system.

References

1. U.S. Dept of Energy, DOE/METC 87/0255, DE87006493, Oct., 1987.
2. Skerret, P.J., "Fuel Cell Update", *Popular Science*, 89-91, 120-1, June, 1993.
3. Lim, H.S. and Winnick, J., *J. Electrochem. Soc.*, **131**, 562-8 (1984).
4. Alexander, S., and Winnick, J., *1990 AIChE Annual Meeting*, Chicago, IL., 1990.
5. Alexander, S., and Winnick, J., *Sep'n Sci. and Tech.*, **25**, 2057-72 (1990).
6. Weaver, D., and Winnick, J., *J. Electrochem. Soc.*, **134**, 2451-58 (1987).
7. Weaver, D., and Winnick, J., *J. Electrochem. Soc.*, **138**, 1626-37 (1991).
8. Banks, E., and Winnick, J., *J. Appl. Electrochem.*, **16**, 583-90 (1986).
9. White, K.A., and Winnick, J., *Electrochim. Acta*, **30**, 511-516 (1985).
10. EPRIEM-1333, *Assessment of Sulfur Removal Processes for Advanced Fuel Cell Systems, Final Report*, C.F. Braun and Co., Alhambra, CA, Jan., 1980.
11. Vidt, E.J., DOE/METC DE-AC-21-81MC16220, DE82013942, Westinghouse, Dec., 1981.
12. Focht, G.D. et. al., DOE/MC/121166-2163, DE86016041, July, 1986.
13. Lyke, S.E., DOE/MC/19077-1803, DE8500961, Battelle Pacific Northwestern Laboratories, Jan. 1985.
14. Winnick, J., Quarterly Progress Report #13, DOE grant DE-FG-91PC91288.
15. Winnick, J., Quarterly Progress Report #11, DOE grant DE-FG-91PC91288.
16. Weaver, D., and Winnick, J., *J. Electrochem. Soc.*, **139**, 492-498 (1992).
17. Alexander, S., *Ph.D. Thesis*, Georgia Institute of Technology, Atlanta, GA, 1992.
18. Winnick, J., Quarterly Progress Report #6, DOE grant DE-FG-91PC91288.
19. Winnick, J., Quarterly Progress Report #8, DOE grant DE-FG-91PC91288.
20. Reed, James S., Introduction to the Principles of Ceramic Processing, John Wiley & Sons, New York, 1988.
21. Niu, Y., Viani, F., and Gesmundo, F., *Corrosion Science*, **36**(5), 883-900 (1994).