DOE/PC/92/20--T6

Quarterly Report

ADVANCED COAL LIQUEFACTION

To

PITTSBURGH ENERGY TECHNOLOGY CENTER

January 1, 1994
to
March 31, 1994

DE-AC22-93PC92120

Media and Process Technology, Inc.
1155 William Pitt Way
Pittsburgh, PA 15238

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

Summary

This project investigated the use of ceramic membranes to improve liquefaction processes to meet both economical and environmental requirements. The separation of model compounds with a series of modified membranes were complete for Yr. I. The experimental system is presently under modification for performing the catalytic membrane reaction. In this quarter, we summarized the Yr. I experimental result as quarterly report to satisfy the contractual reporting requirement.

A series of 1" and 10" long membranes were modified through the CVD method to reduce the pore size. These tubes were characterized by He and N₂ permeation as well as He/SF₆ separation. The He and N₂ permeances decreased with reducing pore size and porosity. The coronene and compound #11 mixture separation were performed in 10-inch long membranes.

The model compound chosen for the catalytic membrane reaction was NBBM (naphthyl-bibenzyl-methane). The hydrogenolysis of this compound will generate toluene which can be selectively removed by the modified membrane. The NBBM/toluene separation was performed in 1" long modified membranes.

The GC calibration of NBBM, coronene, compound #11 and toluene were established and gave good accurate analysis. The results were accurate and reproducible using wide board capillary column with appropriate GC conditions.

The coal-liquid separation through micropores ceramic membranes could be described by an ultrafiltration model. Two transport phenomenons, molecular diffusion and convection, were the most important mechanisms. The hindrance factors were necessary of these mechanisms to evaluate the separation performance of membrane and to design the catalytic membrane reactor. The hindrance factors can be calculated from that rejection and permeate flux based on the simplified Niemi-Palosaari method.

1. Introduction

Successful use of coal liquids as transportation fuel depends on the efficiency of coal liquefaction. Coal liquids contain polycyclic aromatics, which are not only bioactive but also present potential difficulties in upgrading processes and storage. The efficiency of liquefaction can be improved by (a) avoiding regressive reactions in coal liquefaction which produce heavy residue; or (b) selectively hydrocracking the polycyclic aromatics with minimum use of hydrogen and minimum production of light gas. These avenues can potentially be accomplished via the use of ceramic membranes as reactors, which can selectively remove the desired products during liquefaction processes and upgrading. Thus the regressive reaction can be inhibited and the excessive hydrocracking of products can be prevented. Under the funding of Pittsburgh Energy Technology Center, US

DOE, we have initiated a research program focusing on the separation of coal liquids using selected model compounds.

Since the molecular diameter of coal asphaltenes is smaller than that of petroleum asphaltenes, membranes with $<40\text{\AA}$ pore diameter are required to demonstrate the concept proposed. The objective of this project is to modify the membrane to the range of 6 to $15\text{\AA}$. Separation study with selective model compounds was performed to confirm the separation efficiency. Then a membrane reactor would be fabricated with the modified membranes for feasibility study using coal liquid as well as synthetic mixtures of model compound. This project would address the use of ceramic membranes to improve liquefaction processes to meet both economical and environmental requirements. This report is focused on the application of modified membrane to separate synthetic mixtures.

2. Experiment

2.1 Membrane preparation and characterization

The pore size of the $40\text{\AA}$ γ -alumina membrane was reduced by chemical vapor deposition (CVD). Silicate was deposited on the γ -alumina layer using tetraethyl orthosilicate (TEOS) as a pre-cursor agent. TEOS was carried by bubbling a He and O_2 mixture through a vaporizer. The membranes were modified by varying the deposition time for selected temperatures, pressures, and flow rates of the carrier gas.

The modified membranes were characterized using a pore size analyzer and the gas permeation of He and N_2 at room temperature. The 10" long membranes were also characterized by the He/ SF_6 mixture separation. A bench-top gas permeation/separation unit was built as a pre-screening tool for evaluating the separation efficiency of the modified membranes.

2.2 Analysis of Model Compounds

GC Setup

A HP 5890 GC and Chemstation were used to analyze the model compounds. The GC configuration is summarized in Table 1. Capillary column with 30 ft long was used to separate model compounds of the precision. The analysis was further improved by using a wide-board column. With a larger sampling size, the relative error in the area counts was thus reduced. In order to repeat the same injection volume every time, a chaney adaptor was used to minimize human error.

Coronene in Toluene

A methodology was developed to analyze coronene dissolved in toluene. A 0.0335 wt% of coronene was prepared by dissolving coronene in toluene at room temperature. Part of this solution was diluted with toluene to prepare two more concentrations, 0.0223 wt% and 0.01604 wt%.

Figure 1 shows the chromatography of coronene/toluene calibration. The first big peak was toluene at ~3.5 minutes and coronene came out at 25.4 minutes. With splitless purge by a 20 second delay, the solvent peak was much less and had no tailing. It gave very good separation of the coronene and solvent.

Figure 2 shows the coronene calibration curve and statistical error analysis using a narrow-board column. The uncertainty is about 0.005 wt% with 95% confidence. Our experiment showed that the area counts of coronene were always scattered even in the same sample. Figure 3 shows the results of the GC analysis using a wide-board column. The uncertainty actually became worse. The error was about 0.015 wt% at the concentration of 0.06 wt%, compared to the previous error of the narrow board. It was suspected that coronene was not completely dissolved in toluene causing the scattered results even in the same sample bottle.

Coronene in Tetralin

Another solvent, tetralin, was used to desolve coronene because it was H-donor solvent and commonly used in coal liquefaction. The solubility of coronene in tetralin was higher than it in toluene. A 0.111 wt% of coronene in tetralin was prepared and tested in GC analysis. The GC calibration results showed that coronene in tetralin gave the best calibration curve. Figure 4 shows that the average maximum error is less than ± 0.002 wt.% within the range from 0.02 to 0.12 wt.% of coronene.

Compound #11 in Toluene

The compound #11, 1,4 Diethyl-2-[(2'-methoxyphenyl)thio]benzene, was provided by PETC. The compound was completely dissolved well in toluene. The GC calibration of the compound # 11/toluene mixture using a wide-board capillary column showed a good consistent analysis. Figure 5 shows the calibration results. The maximum error was within ± 0.02 wt%.

NBBM/Toluene in Tetralin

The model compound, NBBM (naphthyl-bibenzyl-methane, #9 on the list of model compounds), was purchased from TCI America, Portland, OR 97203. NBBM was dissolved very well in tetralin at room temperature. Two samples were prepared. One was 1.9 wt% of toluene in tetralin, and the other was 3.6 wt% of toluene and 0.51 wt% of NBBM in tetralin. One of the difficulties in GC analysis was that the boiling point of tetralin was between those of toluene and NBBM. In order to prevent large amount of the solvent (i.e. tetralin) saturating the FID of GC instrument, the injected sample needed to be purged before entering the GC

column. However, during the purge, toluene would be purged out before tetralin because of the lower boiling point of toluene. Thus no or very low toluene could be measured. This was solved by modifying the temperature of injection port and the procedure of purge. After several trials and errors, the sample containing toluene and NBBM could be measured simultaneously in less than 20 minutes.

Figure 6 shows the chromatography of NBBM/toluene in tetralin solution using a wide-board column. The retention of toluene was at ~2 minutes and NBBM was about 19 minutes. The tetralin appeared in the middle of chromatography, whose retention time covered from 6 to 18 minute. Those peaks did not interfere of toluene and NBBM, and were ignored in compositions analysis. The calibration curve of NBBM was shown in Figure 7. The reproducibility of the GC analysis was excellent. The maximum error was estimated to be less than 0.005 wt%. Figure 8 shows the calibration curve of toluene. The reproducibility was excellent and the error was less than ± 0.05 wt%.

2.3 Single component permeation

Figure 9 shows the schematic of the liquid permeation and mixture separation system. The solvent was delivered by a HPLC pump. The flow rate was about 200 cc/min and circulated back to the reservoir. The feed pressure was adjusted by a back pressure regulator at the reject of membrane module, while the permeate was open to atmosphere.

All membranes were heated to 300°C in a N₂ flow inside the SS module overnight to remove any moisture trapped inside the pores prior to the experiments. Toluene and tetralin fluxes were obtained by measuring the weight of permeate collected for a period of time at a given transmembrane pressure, ranging from 100 to 800 psi. The membrane was purged with N₂ until the solvent was propelled out of the module before switching to the next solvent.

The liquid volume can be calculated from the weight and liquid density at room temperature. The permeation was taken at 20 and 80°C and could last from several hours to two days dependent on the membranes. The permeance (l/m²/hr/atm) was calculated from liquid volume, membrane surface area and transmembrane pressure.

2.4 Mixture separation

After the toluene and tetralin permeation measurement, the mixture separation was performed with the same membranes. The mixture separation was also carried out at 20 and 80°C. The calculation of pure-component permeance was applied to the mixture by assuming the mixture density equal to that of pure liquid since the concentration of solute was very low. The samples, including permeate and reject, were collected in bottles and analyzed by GC. Since the permeate flow rate (<1 cc/hr) was very small compared to the volume of the reservoir (~ 1 liter), the feed concentration change was assumed to be negligible. To assure the feed concentration was accurate, the feed concentration was

analyzed when each permeate sample was collected. Each sample was analyzed 2 to 4 times to ensure accuracy.

Mixtures of ~0.1 wt.% coronene/tetralin and ~0.8 wt% compound #11/toluene were prepared to test the performance of 10" long modified membranes. The separation of the mixture of toluene (~ 4 to 5 wt%)/tetralin and NBBM (~0.5 wt%)/tetralin was performed in a series of 1" long modified membranes.

3. Results and Discussion

3.1 Characteristics of modified membranes

Seven 10" long membranes (including one 40Å un-modified membrane) were characterized using the He and N₂ permeations and the separation of He/SF₆ mixture. Table 2 shows the results. The He and N₂ permeances of these modified membranes were gradually reduced by different CVD conditions. Pore diameter was also measured by the pore size analyzer. Membranes with pore diameters of less than 25Å fell below the quantification limits of the pore size analyzer. The pore size of these membranes can only be estimated from other techniques, such as He, N₂ permeation and He/SF₆ separation. The kinetic diameters of He, N₂ and SF₆ are 2.6, 3.64 and 5.5Å, respectively. All modified membranes showed poor separation for He/SF₆ and the He/N₂ ratio near 1~2 indicating that the pore diameter should be larger than 5.5Å since the separation factor did not exceed Knudsen diffusion (He/SF₆ = 6.0, He/N₂=2.6).

Another explanation for low separation factor is that it is possible that surface flow of N₂ and SF₆ becomes significant in this pore size range at room temperature. In addition, the absorbed-moisture clogs the small pores which are accessible for He. Since it is exposed to room air before it is packed in the module, it may have moisture-filled small pores. Thus, most of He permeation can be blocked. The permeations of He, N₂ and SF₆ only go through large pores, which causes low separation efficiency.

Table 3 shows the results of 1' long modified membranes with different pore diameters. Membranes with a pore diameter larger than 25Å could be estimated by a pore size analyzer. Pore diameter below 25Å could only be indicated by He permeances roughly.

3.2 Single component permeation

Table 3 and 4 summarizes all the liquid permeation results of 1" long membranes at 20°C and 80°C, respectively. All liquid permeances follow the same trend of He permeances and pore sizes. The permeance difference of toluene and tetralin is due to (1) the viscosity; (2) molecular size. The permeances in 40Å pore membrane indicates that it is most likely due to viscosity since both molecules should be able to permeate through without any hindrance.

CVD modification not only reduces pore size but also porosity. This can be shown by the He permeances. Assuming all pores are still accessible by He, the decrease

of He permeance is primarily due to porosity reduction. From the pore size analysis, the pore diameters of these tube are still larger than the kinetic diameters of toluene and tetralin. Figure 10 shows the liquid permeance vs. He permeance. As indicated from the slope of toluene, the decrease of permeance is still primarily due to porosity reduction. However, from the slope of tetralin, the decrease of permeance may be due to both pore size and porosity. Hence, there may be some hindrance effect on tetralin diffusion.

3.3 Mixture separation

Coronene

Coronene is chosen because it is the molecules of a rigid frame (groups of aromatic ring) and symmetrical shape (no steric effect). From the diffusion viewpoint, coronene can imitate the hard-sphere particle in separation study. The interpretation and the future modeling of the membrane separation can be easily simplified.

Table 5 lists the separation results of coronene/tetralin mixture, and the permeances of the the mixture, toluene and tetralin at room temperature. The permeances significantly decreased as the pore size and the porosity decreased. The permeation of tetralin in Si464 was not measurable, thus the coronene/tetralin separation could not be measured. Generally, the tetralin permeances were 5~10 times less than those of toluene due to the viscosity difference and the size of molecules. The rejection of coronene in Si478 gave the best value, up to 53%; however, the flux was almost 100 times lower than that of a fresh membrane. Pore size analysis showed that the majority of pores for Si478 were less than 26Å. The rejection was also decreased with increasing Δp . This indicated that the high flux (due to high Δp) might cause concentration polarization. The coronene concentration in the permeate increased due to higher concentration gradient. Hence the rejection was reduced.

The kinetic diameters of coronene and tetralin are not available from literature. The kinetic diameter of benzene and cyclohexane are 5.85Å and 6.0Å, respectively. So, the largest kinetic diameter of coronene is estimated to be ~16Å (3 benzene rings), and that of tetralin at near 12Å (benzene+cyclohexane). Therefore, the kinetic diameter difference between coronene and tetralin may be less than 4Å. The separation of these two compounds cannot be effective. Since Si478 gives the best separation performance, the median pore diameter of Si478 is estimated to be between 10 and 20Å. Since no tetralin flux is measurable in Si464, the median pore diameter is estimated less 10Å.

Compound #11

This compound contained sulfur, which represented one of heteroatom compounds in coal liquids. The boiling point was 181~182°C at the pressure of 3 mm Hg. Table 6 summarizes the separation results of the compound #11/toluene mixture in three membrane tubes with different pore diameters and the toluene permeance at room temperature. The rejection of compound #11 in Si478 gave the

best value, up to 35% at $\Delta P=400$ psi; however, the flux was near three times lower than that of a fresh membrane. For Si417 and the 40Å membranes, the rejection were 27% and 22%, respectively, at $\Delta P=100$ psi. Generally no separation was observed at higher pressures and there was no significant difference between these two membranes. It might have been due to the concentration polarization because of the high flux across membrane. The local concentration of the compound #11 near the membrane surface might be higher than that in the bulk feed stream. Since the rejection was calculated based on the concentrations in the bulk feed (not a good assumption), these values were likely under estimated.

The molecular weight of the compound #11 is 272 g/mole, and its kinetic diameter is not available from literature. From the molecular structure, it is difficult to estimate its size because the molecule is linear and flexible. The median pore diameter of Si478 is estimated to be between 10~20 Å (from the coronene separation above), which may not be able to provide complete separation. That means, the separation of toluene and compound #11 cannot be very effective using such membrane.

The separation of compound #11 was not investigated furthermore because (a) the supply was limited. (it was the intermediate product of the other project of PETC); (b) the chemical properties and the reaction pathway were not well established.

NBBM

NBBM is selected because it is commercially available, and can be used as a candidate for the catalytic reaction as following.

One of the products from the hydrogenolysis of NBBM is toluene. In the catalytic membrane reactor, the toluene can be selectively removed to shell side. Thus the conversion of NBBM is enhanced. This reaction represents one of the typical coal-liquid upgrading reactions, hydrogenolysis. Therefore, the separation selectivity of toluene and NBBM becomes crucial in the modified membrane. The criterion of the future membrane modification will base on the selectivity of toluene from NBBM through size exclusion.

NBBM size vs pore diameter

Based on the lowest energy conformation of the molecule at coal liquefaction temperature, there are two most probable dimension of NBBM molecule, 7.7Å X 6.4Å X 20.2Å (stretched conformation) and 11.3Å X 7.7Å X 13.0Å (most compact conformation)¹. The stretched conformation can enter pores having diameter greater than 7.7Å and a length of greater than 20.2Å. The most compact conformation can enter pores having a diameter greater than 11.3Å and a length

greater than 13.0Å. Therefore, all NBBM should be able to enter the pores with diameter greater than 13.0Å and a length greater than 20.2Å.

Temperature effect

The results of the mixture separations using 1" modified membranes are summarized in Tables 7 and 8 at 20 and 80°C, respectively. At 20°C, the rejection of NBBM was 100% in Si279 and Si284. However the permeance was almost two order of magnitudes lower than that of un-modified membrane due to pore size and porosity reduction. For those pore size less than that of Si284 (Si272 and Si276), even the tetralin could not penetrate, not to mention NBBM.

At an elevated temperature (i.e. 80°C), in general, the flux increased because the viscosity decreased with the temperature (Table 8). The rejection in Si279 and Si284 were reduced from 100% to only 30 to 70% at 80°C. Similar trend also was observed in Si286 and un-modified membranes. Normally, all molecules would become more flexible and oscillate vigorously at elevated temperature, hence they gave a wider distribution of the kinetic diameters. The membranes also contained a pore size distribution. Therefore, the probability of the NBBM molecules entering pores would increase with the temperature. For a given mean pore size of membrane, the rejection always decreased in a certain range with increasing temperature.

Transmembrane Pressure effect

The higher the transmembrane pressure (ΔP), the higher the flux. Consequently, high flux may induce two effects, which can influence the rejection. The concentration polarization becomes more significant due to the higher throughput of the permeate. Since the rejection is calculated from the bulk feed, the value is possibly underestimated, i.e. a lower apparent rejection is observed from experiment. On the other hand, a higher flux causes a higher flow velocity inside the pores. Since the pore shape is non-straight tunnel (tortuosity ~ 3.95), the macromolecules may be easily trapped inside the pores at a higher flow velocity. Therefore, the apparent pore size is reduced and the rejection increases.

The concentration polarization is the function of Reynold and Peclet numbers (i.e. flow rate and concentration). The trap effect is reversible, if there is no interaction force between macromolecules and the membrane. That means, the apparent pore size can be recovered because the trapped molecules will be carried away when the flow velocity decreases due to less ΔP . Therefore, depended on the characteristics molecules and membrane as well as operating conditions, the rejection may be either higher or lower at a higher transmembrane pressure. Experimentally, there may is no way to distinguish them. That is why our separation results (Tables 5-8) give us no explicit conclusion.

Toluene rejection

Theoretically, the rejection of toluene should be negative (i.e. the toluene concentration in the permeate is higher than feed) because the toluene diffusivity

is higher than that of tetralin at all temperatures. As shown in Table 7 and 8, some of the toluene concentrations of permeate are higher than those in the feed, but not all. The rejection determined by the experiment may be difficult to show this trend because of (a) the uncertainty of the GC analysis error, and (b) the influence of co-diffusion with NBMM in the pores.

A solution of toluene alone desolved in tetralin was prepared for mixture separation on the same membranes. The purpose was to eliminate the influence of NBMM during separation. It contained higher concentration (~7 wt%) of toluene to increase the GC sensitivity. The separations were carried out at the same condition as that of NBMM. The rejection of toluene mixture are shown in Figure 11 and 12 at 20 and 80°C, respectively. As one expected, the toluene rejections were near zero or negative in the range of 100 to 300 psi at both 20 and 80°C.

3.4 Ultrafiltration Theory : Statistical-Mechanical Model

The transport phenomenon of macromolecules in liquid-filled pores (membrane) is different from that of gas-phase. In the case of coal-liquid separation using microporous ceramic membrane, it is in the category of ultrafiltration. That is, the molecular weight is in the range of 300 ~ 500. The pore diameter of membrane is in the range of 10 to 30 Å. Basically, two mechanisms play in this domain, molecular diffusion and convective flow. Molecular diffusion is determined by the characteristics of solute and solvent as well as their interaction forces, such as electrical potential. Convective flow is simply the function of hydrodynamics, such as viscosity and pressure. Both are also the function of temperature. When these two mechanisms apply to porous media, each transport mechanism is further modified by the pore size, pore shape and pore density (or porosity) of the membrane as well as any interaction forces between solute and membrane surface. Usually, they are expressed by the hindrance factors of diffusion and convection. Theoretically, these factors can be calculated based on the ratio of molecular size to pore diameter and further modified by the related interaction forces, if any. However, since the mean pore diameter (< 30Å) of our modified ceramic membrane is unable to be measured by pore size analyzer or any other reliable methods, it is not possible to calculate hindrance factors from modeling. Experiment results only give overall rejection, any interaction forces may exist but is not measurable with current setup. In addition, that our modified membranes are inherited pore size distribution and irregular pore shape (tortuosity ~ 3.9) makes the estimation of hindrance factors more difficult.

Mason and Lonsdale² proposed a statistical-mechanical model, which gave a general description of the hard-sphere solute/solvent transport in porous media. Ultrafiltration was one of its special case. The model assumed solute molecule was rigid, sphere, uncharged particle. The porous membrane was chemically inert, straight cylindrical pores. The solvent was assumed to be a continuous phase. Niemi and Palosaari³ further simplified this model and presented an experimental method to calculate these parameters, which could properly describe a given membrane separation. They derived equations to co-relate the experimental data and theory, then directly calculated two important parameters,

effective diffusivity (D_{eff}) and effective convective flow through membrane. Once the bulk diffusivity (D_{∞}) of solute was known (from literature or experiment), the hindrance factor of diffusivity (H_d) could be calculated for a given membrane system by Equation 2. Based on this semi-empirical approach, the advantage was that all parameters could be determined without knowing pore diameter and molecular size.

$$D_{eff} = H_d \cdot D_{\infty} \quad [2]$$

Experimentally, the rejection ($R, \%$) is obtained from the compositions of feed and permeate by GC analysis (Eqn. 3). The permeate flux ($J_v, m^3/m^2/s$) is varied with pressure drop across the membrane. According the equation 4, the reflection coefficient (σ) and solute diffusive permeability ($P, m/s$) can be calculated from the slope and intercept, respectively. Equation 5 and 6 are used to calculate the D_{eff} and hindrance factor of convective flow, W , respectively.

$$R = 1 - \frac{c_{pm}}{c_{fm}} \quad [3]$$

$$\frac{1}{R} = \frac{P}{\sigma} \cdot \frac{1}{J_v} + \frac{1}{\sigma} \quad [4]$$

$$D_{eff} = P \cdot L \quad [5]$$

$$W = 1 - \sigma \quad [6]$$

where c_{pm} : concentration of permeate near membrane surface (kg/m^3)

c_{fm} : concentration of feed near membrane surface (kg/m^3)

L : pore length or effective membrane thickness (m)

Effective diffusivities, hindrance factors of diffusion and convection

The model was applied to experimental data, and the results were shown in Figure 13 - 18 based on Eqn 4. This correlation only gave solute diffusion permeability (cm/s) from the slope. Although the pore size of membrane support was very large ($> 10 \mu m$), its contribution of resistance of liquid transport might still be significant due to its thickness ($\sim 1 mm$). Therefore, the effective diffusivity (D_{eff}) could not be estimated due to the lack of total effective membrane thickness. However, if we assumed the effective thickness was about $5 \mu m$ (i.e. top layer), then the diffusivity was the thickness times the solute diffusion

permeability. Table 9 lists the calculated results. The diffusivities were quite scattered but in the range of $10\text{E-}9$ (cm^2/s) of modified membranes.

The reflection coefficient is always between 0 and 1. As shown in Table 9, the numbers are scattered and inconsistent with membrane pore size. However, it is possible due to the calculation error since it is derived from the intercept, which always inherits bigger errors according to this model.

Since the size of toluene is much smaller than the membrane pore diameter, both hindrance factors can be assumed ~ 1 . That means, the effective diffusivity and convection are assumed to be closed to those in the bulk solution.

4. Future Work

In the second year, the NBBM/tetralin separation will be performed at the pressures and temperatures near coal liquefaction using the same membranes. More modification of membranes may be required if the separation efficiency is lower at higher temperature. The pore diameter of membranes will be further reduced by CVD. The catalytic hydrogenolysis of NBBM will be also carried out to demonstrated the feasibility of membrane reactor in coal liquefaction and upgrading.

References

1. Communication letter of Dr. Jean-Loup Faulon at Sandia National Laboratories, May 25, 1994.
2. Mason, E. A. and Lonsdale, H. K., "Statistical-Mechanical Theory of Membrane Transport," J. Membrane Science, vol. 51, p. 1 (1990).
3. Niemi, H and Palosaari, S., "Calculation of Permeate Flux and Rejection in Simulation of Ultrafiltration and Reverse Osmosis Processes," J. Membrane Science, vol. 84, p. 123 (1993).

Table 1 : GC Configurations and Conditions

• **HP 5890A**

Narrow Board

- Column : Supelco SPB-5 Fused Silica Capillary, 30 m, 0.32 mm ID, 0.25 μ m film Thickness
- Injection port : 300°C, splitless, 20 sec. purge delay
- Detector : FID, 375°C
- Oven : Temperature programming, Hold 2 min. at 80°C , 20°C/min to 375°C, hold 12.75 min.
- Sampling : 1 μ l, Hand injection using chaney Adaptor, deep injection hold 10 sec. before removing syringe.

Wide Board

- Column : Supelco SPB-5 Fused Silica Capillary, 15 m, 0.53 mm ID, 0.5 μ m film Thickness
- Injection port : 200°C, splitless, 15 sec. purge delay
- Detector : FID, 375°C
- Oven : Temperature programming, Initial 80°C, hold 2 min. at 80°C , 20°C/min to 315°C, hold 6.25 min.
- Sampling : 1 μ l, Hand injection using chaney Adaptor, deep injection hold 10 sec. before removing syringe.

Table 2 : Characteristics of 10' long Modified Membranes

Mem.	<u>Permeance (m³/m²/hr/atm)</u>		He/N ₂	<u>SF₆ (%)</u>		S.F. ^a
	He	N ₂		Feed	Permeate	
50Å ^b	140.0	70.0	2.0	-	-	-
Si417	62.3	26.0	2.4	-	-	-
Si478	20.7	20.3	1.0	10.07	8.9	1.15
Si451	2.11	0.979	2.2	10.07	9.3	1.10
Si472	0.505	0.247	2.0	10.07	5.9	1.82
Si471	0.479	0.258	1.9	10.07	5.7	1.85
Si464	0.042	0.019	2.2	10.07	8.8	1.16

a Separation Factor calculated by concentration. Knudsen S. F. He/SF₆= 6.0

b The He and N₂ permeance are typical values.

**Table 3 : Permeations of Modified Membranes
at Room Temperature (1")**

Mem. ID	Pore D. (Å)	He Permeance (m ³ /m ² /atm/hr)	ΔP (psi)	Liquid Permeance (l/m ² /atm/hr)	
				Toluene	Tetralin
Un-modified	40	240~300	100	1.8478	0.2017
			200	2.0915	0.2177
			300	2.2148	0.2483
			400	1.7437	0.2899
Si286	36	190.0	100	1.3993	0.0542
			200	1.5253	0.0638
			300	1.6235	0.0550
			400	1.5446	0.0666
Si284	28	115.0	100	0.67	-
			200	0.65	-
			300	0.86	0.0195
			400	0.97	0.0210
Si279	<30	92.2	100	0.2502	-
			200	0.2641	0.0094
			300	0.2632	-
			400	0.2868	0.0089
Si272	<29	40.0	100	0.15	0.0
			200	0.16	0.0
			300	0.17	0.0
			400	0.17	0.0
Si276	-	35.0	100	0.10	0.0
			200	0.10	0.0
			300	0.11	0.0
			400	0.11	0.0

Table 4 : Permeations of Modified Membranes at 80°C (1")

Mem. ID	Pore D. (Å)	He Permeance (m ³ /m ² /atm/hr)	ΔP (psi)	Liquid Permeance (l/m ² /atm/hr)	
				Toluene	Tetralin
Un-modified	40	240~300	100	4.5033	0.7759
			200	5.0690	0.8412
			300	5.4885	0.8732
			400	6.0855	0.9939
Si286	36	190.0	100	2.6102	0.5440
			200	2.7451	0.4468
			300	2.9865	0.4889
			400	3.4905	0.5209
Si284	28	115.0	100	1.2479	0.1542
			200	1.4363	0.1665
			300	1.5199	0.1999
			400	1.6881	0.2053
Si279	<30	92.2	100	0.8544	0.0907
			200	0.9334	0.0907
			300	0.9648	0.0967
			400	1.0110	0.1021
Si276	-	35	100	0.1946	0.0
			200	0.1994	0.0
			300	0.2006	0.0
			400	0.2004	0.0

Table 5 : Separation of Coronene/Tetraline Mixtures at Room Temperature (10')

Mem.	Pore (Å)	Δp (psi)	Coronene Conc. (ppm)		Rejection (%)	Permeance (l/m ² /hr/atm)		
			Feed	Permeate		Cor/Tetra Mix	Tetralin	Toluene
Fresh	40	100	966	877	9.2	1.137	1.1375	10.500
		200	1026	939	8.5	1.057	1.2643	9.340
		300	1004	972	3.2	1.056	1.2573	8.430
		400	1029	954	7.3	1.039	1.2317	-
Si417	34	100	1037	767	26.0	0.1568	0.3244	2.3673
		200	1015	888	12.5	0.1747	0.2947	1.9148
		300	970	934	3.7	0.1739	0.2797	1.5941
		400	989	847	4.2	0.1626	0.2717	1.3691
Si478	<26	100	987	461	53.3	0.0082	0.0266	0.1007
		200	947	719	24.1	0.0084	0.0238	0.1536
		300	1011	604	40.3	0.0099	0.0226	0.1518
		400	976	684	30.0	0.0121	0.0203	0.1477
Si464	<10	400	N/A	N/A	N/A	0.0	0.0	0.0098
		600	N/A	N/A	N/A	0.0	0.0	0.0073
		800	N/A	N/A	N/A	0.0	0.0	0.0068

Table 6 : Separation of Comp # 11/Toluene Mixtures at Room Temperature (10')

Mem.	Pore (Å)	Δp (psi)	Comp.#11 Conc. (wt%)		Rejection (%)	Permeance (l/m ² /hr/atm)	
			Feed	Permeate		Mixture	Toluene
Fresh	40	100	0.876	0.639	27.1	1.3268	1.3043
		200	0.790	0.740	6.3	1.1824	1.2168
		300	0.816	0.700	14.2	1.1355	1.1778
		400	0.809	0.817	~0.0	1.1307	1.1024
Si417	34	100	0.867	0.673	22.4	1.2105	2.3673
		200	0.813	0.782	3.8	1.1753	1.9148
		300	0.860	0.780	9.3	1.0469	1.5941
		400	0.821	0.820	0.0	1.0136	1.3691
Si478	<26	100	0.817	0.666	18.5	0.2274	0.3917
		200	0.785	0.624	20.6	0.2121	0.3611
		300	0.755	0.628	16.8	0.2172	0.3451
		400	0.869	0.566	34.9	0.2130	0.3279

Index

Mem. ID	ΔP (psi)	Mixture Perm. (l/m ² /atm/hr)	Concentration (wt%)				Rejection(%) NBBM
			Feed		Permeate		
			Toluene	NBBM	Toluene	NBBM	
Un-modified	40	0.082	-	0.38	-	0.28	26
	80	0.064	-	0.39	-	0.24	38
	100	0.049	-	0.36	-	0.28	22
Si286	100	0.0321	4.63	0.28	4.53	0.18	36
	200	0.0418	4.63	0.28	4.78	0.15	45
	300	0.0428	4.63	0.28	4.65	0.14	48
	400	0.0459	4.63	0.28	4.70	0.12	56
Si279	200	0.00063	4.33	0.34	0.96	0.0	100
	300	0.00057	4.48	0.36	1.22	0.0	100
	400	0.00060	4.60	0.37	1.45	0.0	100
Si284	400	0.0099	4.05	0.33	0.45	0.0	100
Si272	N/A	N/A					
Si276	N/A	N/A					

10

Mem. ID	ΔP (psi)	Mixture Perm. (l/m ² /atm/hr)	Concentration (wt%)				Rejection(%) NBBM
			Feed		Permeate		
			Toluene	NBBM	Toluene	NBBM	
Un-modified	100	0.6029	4.32	0.33	4.21	0.28	14
	200	0.6554	4.32	0.33	4.36	0.29	12
	300	0.6782	4.32	0.33	4.17	0.27	17
	400	0.7151	4.32	0.33	2.87	0.18	43
Si286	100	0.2902	4.57	0.28	4.47	0.22	22
	200	0.3088	4.57	0.28	4.77	0.22	22
	300	0.3330	4.57	0.28	4.81	0.20	28
	400	0.3346	4.57	0.28	4.87	0.20	27
Si279	100	0.0550	4.44	0.30	4.35	0.21	30
	200	0.0634	4.44	0.30	4.46	0.18	40
	300	0.0703	4.44	0.30	4.50	0.14	53
	400	0.0743	4.44	0.30	3.60	0.10	67
Si284	100	0.0529	4.05	0.33	3.91	0.22	34
	200	0.0712	4.05	0.33	3.89	0.17	47
	300	0.0909	4.05	0.33	3.76	0.16	51
	400	0.1418	4.05	0.33	3.53	0.10	68
Si276	N/A	N/A					

Table 9 : Effective Diffusivity and Reflection Factor of NBBM in Tetralin

Temp. (°C)	Mem. ID	Diffusivity*(cm ² /s)	Reflection Factor
20	40Å	3.9E-9	0.55
	Si286	1.9E-9	0.58
	Si284	-	-
	Si279	-	-
80	40Å	1.1E-7	1.16
	Si286	8.8E-9	0.28
	Si284	4.7E-9	0.65
	Si279	8.2E-9	0.76

* Assumed effective layer thickness is 5µm, i.e. Top layer of membrane only.

Figure 1 GC Chromatograph of Coronene in Toluene

**Figure 2 : Calibration of Coronene in Toluene Solvent
in Narrow-board Column**

**Figure 3 : Calibration of Coronene in Toluene Solvent
in Wide-Board Column**

**Figure 4 :The Calibration of Coronene in Tetralin Solvent
In Wide-Board Column**

Figure 5 :The Calibration of Com. #11 in Toluene Solvent

[illegible]

Figure 6 GC Calibration of NBBM and Toluene

Figure 7: GC Calibration of NBBM Desolved in Tetralin

Figure 8: GC Calibration of Toluene Desolved in Tetralin

Figure 9 Schematic of Liquid Permeation/Separation System

Figure 10: The Liquid Permeances vs. He Permeance

Figure 11 : Toluene/Tetralin Mixture Separation at 20°C

Figure 12 : Toluene/Tetralin Mixture Separation at 80°C

Figure 13 : Separation of NBBM//Tetralin Using 40Å Membrane

Figure 14 : Separation of NBBM in Tetralin

Using 40Å Membrane at 80°C

**Figure 15 : Separation of NBBM in Tetralin
Using Si286 at 20°C**

Reflection coefficient = $1/1.7316 = 0.5775$

Solute diffusive permeability = $6.417\text{E-}8 * 0.5775 = 3.706\text{E-}8 \text{ m/s}$

If $L_{eff} = 5\mu = 5.0\text{E-}4 \text{ cm}$

$D_{eff} = 3.706\text{E-}6 \text{ cm/s} * 5.0\text{E-}4 \text{ cm} = 1.853\text{E-}9 \text{ cm}^2/\text{s}$

Figure 16 : Separation of NBBM in Tetralin
Using Si286 at 80°C

Reflection coefficient = $1/3.5214 = 0.284$

Solute diffusive permeability = $6.2228\text{E-}7 * 0.284 = 1.767\text{E-}7\text{m/s}$

If $L_{eff} = 5\mu = 5.0\text{E-}4 \text{ cm}$

$Deff = 1.767\text{E-}5 \text{ cm/s} * 5.0\text{E-}4 \text{ cm} = 8.835\text{E-}9 \text{ cm}^2/\text{s}$

Figure 17 : Separation of NBBM in Tetralin
Using Si284 at 80°C

Reflection coefficient = $1/1.5202 = 0.658$

Solute diffusive permeability = $1.4337\text{E-}7 * 0.658 = 9.43\text{E-}8\text{m/s}$

If $L_{eff} = 5\mu = 5.0\text{E-}4 \text{ cm}$

$D_{eff} = 9.43\text{E-}6 \text{ cm/s} * 5.0\text{E-}4 \text{ cm} = 4.72\text{E-}9 \text{ cm}^2/\text{s}$

Figure 18 : Separation of NBBM in Tetralin
Using Si279 at 80°C

Reflection coefficient = $1/1.3129 = 0.762$

Solute diffusive permeability = $2.1543\text{E-}7 * 0.762 = 1.64\text{E-}7 \text{ m/s}$

If $L_{eff} = 5\mu = 5.0\text{E-}4 \text{ cm}$

$D_{eff} = 1.64\text{E-}5 \text{ cm/s} * 5.0\text{E-}4 \text{ cm} = 8.2\text{E-}9 \text{ cm}^2/\text{s}$