S. K. Lyo

Sandia National Laboratories, Albuquerque, N. M. 87185

(Received 20 May 1996)

Tunneling absorption is calculated in weakly-coupled n-type asymmetric double quantum wells in an in-plane magnetic field using a linear response theory. Photon-assisted tunneling occurs between the ground sublevels of the quantum wells. We show that the absorption threshold, the resonance energy of absorption, and the linewidth depend sensitively on the magnetic field and the temperature.

1. Introduction

Tunneling between two quasi-two-dimensional (2D) layers of electron gases displays many interesting phenomena [1 - 8] and offers new device applications. In this paper, we study photon-assisted tunneling in weakly coupled double quantum well (DQW) structures subject to an in-plane magnetic field (B). Tunneling occurs between the ground sublevels of the QWs which have unequal 2D electron densities $N_1 > N_2$. Higher sublevels are far above the ground sublevels in thin QWs and are not considered here. We find that the absorption threshold energy, the absorption peaks, and the width all depend sensitively on B .

In d.c and a.c. tunneling transport processes in this structure, electrons flow in through one end of a QW, undergo resonant or photon-assisted tunneling through the barrier

between the two QWs, and flow out of the other end of the second QW. This structure was realized recently through the pioneering new technique of creating independent ohmic contacts to closely spaced QWs in DQW structures [9]. In DQW structures with a wide barrier between the wells, the in-plane conductances in the QWs are much larger than the tunneling conductance, yielding negligible potential drop along the current paths inside each QW. The linear driving electric field is in the growth direction perpendicular to the two QWs which are in equilibrium.

In zero magnetic field, the energy-dispersion paraboloids of the two QWs are parallel, offset by the energy mismatch Δ ($\sim$ a few meV) of the ground sublevels of the two QWs as shown in Fig. 1(a) for $k_x = 0$. For nonzero Δ , d.c. resonant tunneling is impossible because momentum and energy conservations cannot be achieved simultaneously on the Fermi surface as can be seen from the fact that the two concentric Fermi circles in Fig. 1(a) do not intersect [1]. However, tunneling can occur through absorption of photons as illustrated schematically by the vertical arrows, which originate from the occupied states of the lower parabola of QW1 and terminate at the vacant states of the upper parabola of QW2. The shaded area indicates degenerate 2D electron gases. The absorption lineshape is sharply peaked at $\hbar\omega = \Delta$, yielding possible applications to infrared-detector devices. The absorption decreases monotonically with increasing temperature (T) due to thermal smearing of the Fermi surfaces.

In an external in-plane magnetic field applied in the x-direction, the in-plane wave vector $\mathbf{k} = (k_x, k_y)$ is still a good quantum number except that the two paraboloids are shifted in $\mathbf{k}$ space relative to each other in the k_y -direction by an amount $\Delta k_y = d / \ell^2$ as shown for $k_x = 0$ in Fig. 1(b) - (f) for increasing B [2]. Here d is the center-to-center distance of the

QWs and $\ell = (\hbar c/eB)^{1/2}$ is the classical magnetic length. Inspection of Fig. 1 implies that the absorption lineshape should change dramatically with increasing B , as will be shown below.

2. Tunneling Absorption

The absorption is given, in a tight-binding model and ignoring spin splitting, by the real part of the tunneling conductivity [2]

$$\sigma_R = \frac{4\pi J^2 e^2 d}{\hbar S} \sum_k \int_{-\infty}^{\infty} \frac{f(z) - f(z + \hbar\omega)}{\hbar\omega} \rho_{1k}(z) \rho_{2k}(z + \hbar\omega) dz, \quad (1)$$

where J is the tunneling integral, $f(z)$ is the Fermi function, $\hbar\omega$ is the photon energy, S is the area of the QWs, and

$$\rho_{ik}(z) = \frac{1}{\pi} \frac{\Gamma_{ik}(z)}{(z - \varepsilon_{ik})^2 + \Gamma_{ik}(z)^2}. \quad (2)$$

The energies are given by

$$\begin{aligned} \varepsilon_{1k} &= \varepsilon(k_x) + \varepsilon(k_y), \\ \varepsilon_{2k} &= \varepsilon(k_x) + \varepsilon(k_y - \Delta k_y) + \Delta, \quad (\Delta k_y = \frac{deB}{\hbar c}) \end{aligned} \quad (3)$$

where $\varepsilon(q) = \hbar^2 q^2 / (2m^*)$ and m^* is the effective mass. In (2), $\Gamma_{ik}(z)$ is given in the Born approximation by $\Gamma_{1k}(z) = \Gamma_1 \theta(z)$ and $\Gamma_{2k}(z) = \Gamma_2 \theta(z - \Delta)$ for short-range (i.e., delta-function) scattering potentials. Here $\theta(z)$ is a unit step function and Γ_1 and Γ_2 are constants.

In zero magnetic field, σ_R in (1) can be approximated as

$$\sigma_R = \frac{2J^2 e^2 d \rho_{2D}}{\hbar^2 \omega S} \frac{\Gamma}{(\hbar\omega - \Delta)^2 + \Gamma^2} \left\{ \frac{1}{\beta} \ln \frac{e^{\beta\hbar\omega} + e^{\beta(\Delta - \mu)}}{1 + e^{\beta(\Delta - \mu)}} \right\}, \quad (4)$$

where $\Gamma = \Gamma_1 + \Gamma_2$, $\beta = (k_B T)^{-1}$, $\rho_{2D} = m^* S / (\pi \hbar^2)$ is the 2D density of states, and $\Delta_>$ is the larger of Δ and $\hbar\omega$. The expression in (4) is exact in the limit $\Gamma_1 \rightarrow 0$ or $\Gamma_2 \rightarrow 0$. The chemical potential μ is a function of N_1 , N_2 , and T .

In an in-plane magnetic field, the field-induced broadening arising from the relative dis-

placement of the dispersion parabolas of QW1 and QW2 is much larger than Γ in a high-mobility structure. Therefore, neglecting damping (i.e., $\Gamma_1 \approx \Gamma_2 \approx 0$), carrying out z , k_x , and k_y integrations in (1), we find

$$\sigma_R = \frac{J^2 e^2}{\pi^2 \hbar^2 \omega \ell \varepsilon (\ell^{-1})} (F(\varepsilon^*) - F(\varepsilon^* + \hbar\omega)), \quad (5)$$

where $\varepsilon^* = \varepsilon(k_y^*)$, $\varepsilon(q)$ (e.g., $q = \ell^{-1}$, k_y^*) and

$$F(z) = \ell \int_0^\infty \frac{dk_x}{\exp[\beta(\varepsilon(k_x) + z - \mu)] + 1} \quad (6)$$

with

$$k_y^* = \frac{1}{2d} \left[\frac{\Delta - \hbar\omega}{\varepsilon(\ell^{-1})} + \left(\frac{d}{\ell}\right)^2 \right]. \quad (7)$$

At zero temperature, the result in (5) reduces to

$$\sigma_R = \frac{J^2 e^2}{2\pi \hbar^2 \omega \ell \varepsilon (\ell^{-1})^2} \left(\sqrt{(\hbar\omega - \hbar\Omega_-)(\hbar\Omega_+ - \hbar\omega)} - \sqrt{(\hbar\omega - \hbar\omega_-)(\hbar\omega_+ - \hbar\omega)} \right), \quad (8)$$

where

$$\hbar\Omega_\pm = \Delta + \left(\frac{d}{\ell}\right)^2 \varepsilon(\ell^{-1}) \pm 2 \frac{d}{\ell} \sqrt{\mu \varepsilon(\ell^{-1})}, \quad (9a)$$

and

$$\hbar\omega_\pm = \left[\Delta - \left(\frac{d}{\ell}\right)^2 \varepsilon(\ell^{-1}) \pm 2 \frac{d}{\ell} \sqrt{(\mu - \Delta) \varepsilon(\ell^{-1})} \right] \theta(\mu - \Delta). \quad (9b)$$

In (8), the square roots are assumed to vanish for negative arguments and $\Omega_\pm$ are the absorption edges. The absorption lineshape has cusps at the energies $\hbar\omega_\pm$. The transitions responsible for the upper and lower absorption edges ($\Omega_\pm$) and the cusps ($\hbar\omega_\pm$) are shown by the four vertical arrows in Fig. 1(b).

3. Numerical Applications and Discussions

The a. c conductance per area $G(\omega)/S = \sigma_R / d$ is evaluated for n-type GaAs/AlGaAs DQWs with unbalanced 2D electron densities $N_1 = 1.74 \times 10^{11}$, $N_2 = 0.95 \times 10^{11} \text{ cm}^{-2}$ with

$\Delta = 2.83$ meV, employing $m^* = 0.067m_0$ (m_0 is the free electron mass), $d = 21.5$ nm, and $J = 0.04$ meV [2]. These parameters are relevant to a DQW structure studied previously for d.c.-magnetotunneling properties experimentally [3] as well as theoretically [2]. The numerical results are displayed in Fig. 2 for several characteristic B 's at $T = 0$, using $\Gamma = 0.3$ meV for $B = 0$ and $\Gamma = 0$ for $B > 0$. The relative positions of the Fermi circles of QW1 and QW2 are schematically shown together with B .

At zero B , the lineshape is quasi-Lorentzian and centered at $\hbar\omega = \Delta$. As B is increased, the inner Fermi circle moves toward the outer circle and the central absorption peak splits into two peaks with two cusps as shown in Fig. 2 at $B = 0.2$ and 0.5 T. As mentioned in the previous section, the positions of the upper and lower cusps are at $\hbar\omega = \hbar\omega_+$ and $\hbar\omega = \hbar\omega_-$, while the upper and lower cutoff energies equal $\hbar\omega = \hbar\Omega_+$ and $\hbar\Omega_-$. The transitions responsible the absorption edges and cusps are shown by the four vertical arrows in Fig. 1(b). The cusps are rounded by damping and thermal broadening. As B is further increased, the inner Fermi circle moves further toward the outer Fermi circle, intersecting the latter tangentially from inside at $B_- = 0.84$ T. At the same time, the lower-energy absorption peak moves toward zero energy, diverging at $\hbar\omega = 0$ at $B = B_- = 0.84$ T. The cusp and the upper cutoff are at $\hbar\omega = \hbar\omega_+$ and $\hbar\omega = \hbar\Omega_+$, respectively, while the quantities $\hbar\Omega_-$, $\hbar\omega_-$ vanish at this B . The divergent d.c. tunneling conductance $G(0)$ arises from the fact that energy-momentum conservations are simultaneously satisfied for tunneling at a maximum number of points in k -space when the two circles intersect tangentially. With further increasing B (e.g., $B = 5.4$ T), the two circles intersect at two points and the d.c. conductance decreases but remains finite. At $B = 5.4$ T, the upper cutoff is given by $\hbar\Omega_+ = 42.5$ meV and is not shown in Fig. 2. Note from Fig. 1 that, above $B > B_- = 0.84$ T, absorp-

tion can be from QW1 to QW2 as well as from QW2 to QW1. The two circles intersect each other tangentially for the last time from outside at $B_+ = 5.57$ T, where the d.c. conductance $G(0)$ diverges again for the same reason as explained above. The conductance $G(\omega)$ diverges as $\omega^{-1/2}$ for $\omega \rightarrow 0$ at $B = B_{\pm}$. The divergence is rounded by damping [2]. In general $B_{\pm}$ is given by $B_{\pm} = \sqrt{2\pi}(\sqrt{N_1} \pm \sqrt{N_2})\hbar c / ed$, where N_1 (N_2) is the larger (lesser) of the two densities. As B is increased beyond $B_+ = 5.57$ T, the two circles separate from each other; the absorption threshold energy becomes larger than zero and rises in energy as shown for $B = 6.0$ T in Fig. 2.

In the absence of damping and at zero temperature, the d.c. conductance $G(0)$ remains zero until B reaches the threshold field $B = B_-$, where it diverges. As B is increased further, $G(0)$ decreases, reaches a minimum, and then increases until it diverges again at $B = B_+$. The d.c. conductance $G(0)$ vanishes for $B > B_+$. In the presence of damping or at finite temperatures, however, the divergences of $G(0)$ become rounded; $G(0)$ drops to zero only gradually below B_- as well as above B_+ [2, 3].

The absorption at finite temperatures is given by (5). The lineshape is displayed in Fig. 3 at several temperatures for the same sample parameters studied in Fig. 2. Sharp absorption edges at zero temperatures are rounded and broadened at finite temperatures due to thermal broadening of the Fermi surfaces.

4. Conclusions

We have employed a linear-response theory to study the interwell-tunneling absorption in weakly-coupled n-type asymmetric double quantum wells (QWs) subject to an in-plane magnetic field. Photon-assisted tunneling occurs between the ground sublevels of the QWs. We have shown that applied magnetic fields alter the threshold energy, the resonance

energy, and the linewidth sensitively.

Acknowledgment --The author thanks Dr. J. A. Simmons for valuable discussions. This work was supported by U.S. DOE under Contract No.DE-AC04-94AL85000.

References

1. J. P. Eisenstein, T. J. Gramila, L. N. Pfeiffer, and K. W. West Phys. Rev. B **44**, 6511 (1991).
2. S. K. Lyo and J. A. Simmons J. Phys.: Condens. Matter **5**, L299 (1993).
3. J. A. Simmons, S. K. Lyo, J. F. Klem, M. E. Sherwin, and J. R. Wendt Phys. Rev. B **47**, 15741(1993).
4. L. Zheng and A. H. MacDonald Phys. Rev. B **47**, 10619(1993).
5. S. K. Lyo, Phys. Rev. B **50**, 4965 (1994).
6. J. A. Simmons, S. K. Lyo, N. E. Harff, and J. F. Klem, Phys. Rev. Lett. **73**, 2256 (1994).
7. J. A. Simmons, N. E. Harff, and J. F. Klem, Phys. Rev. B **51**, 11156 (1995).
8. S. K. Lyo, Phys. Rev. B **51**, 11160 (1995).
9. J. P. Eisenstein, L. N. Pfeiffer, and K. W. West, Appl. Phys. Lett. **57**, 2324 (1990).

Figure Captions

Fig. 1 Relative positions of the energy-dispersion parabolas with concomitant Fermi circles for increasing magnetic fields from (a) to (f). The vertical arrows indicate tunneling absorptions. The four arrows in (b) signify the transitions responsible for the absorption edges at $\hbar\Omega_{\pm}$ and the cusps at $\hbar\omega_{\pm}$.

Fig. 2 Zero-temperature absorption at several characteristic magnetic fields for an asymmetric double-quantum-well structure. The circles denote the relative positions of the Fermi circles of the two QWs. The sample parameters are given in the text.

Fig. 3 Absorption lineshape at several temperatures for $B = 0$ and $B = B_- = 0.84$ T for the same sample parameters as in Fig. 2.

Fig. 1

Fig. 2

Fig. 3

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.