ANL/ET/CP--85330
CONF-950722--17

FABRICATION OF SUPERCONDUCTING JOINTS FOR Ag-CLAD BSCCO
CONDUCTORS*

A. N. Iyer, J. Y. Huang, R. Jammy, and U. Balachandran
Energy Technology Division
Argonne National Laboratory
Argonne, IL 60439

RECEIVED
JAN 24 1995
OSTI

P. Haldar
Intermagetics General Corporation
Latham, NY 12110

July 1995

The submitted manuscript has been authored by a contractor of the U. S. Government under contract No. W-31-109-ENG-38. Accordingly, the U. S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U. S. Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Manuscript submitted for publication in Advances in Cryogenic Engineering, Volume 42, 1995.

*Work at ANL and part of the work at IGC is supported by the U.S. Department of Energy (DOE), Energy Efficiency and Renewable Energy, as part of a DOE program to develop electric power technology, under Contract W-31-109-Eng-38.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

FABRICATION OF SUPERCONDUCTING JOINTS FOR Ag-CLAD BSCCO CONDUCTORS

A. N. Iyer, J. Y. Huang, R. Jammy, U. Balachandran¹, P. Haldar, and J. G. Hoehn, Jr.²

¹Energy Technology Division, Argonne National Laboratory
Argonne, IL 60439, U.S.A.

²Intermagnetics General Corporation
Latham, NY 12110

ABSTRACT

Potential applications of high- T_c superconductors include motors, generators, transmission cables, magnets, etc. At present, resistive connections are used to connect various high- T_c components for such applications. However, to improve efficiency, it is imperative that the resistive connection be replaced by a true superconducting joint. Using a novel etching technique, we have fabricated superconducting lap and butt joints between Ag-clad BSCCO conductors. The Ag sheath from one side of the tape was selectively etched to expose the underlying superconductor core. Joints were formed by bringing the two tapes together and heat treating them. Detailed microstructural analysis and current transport measurements of the joints have been performed. Critical current (I_c) through a monofilament lap- and butt-joint were 10 and 23 A, respectively. I_c within the joint for mono- and multifilament conductors were 37 and 21 A, respectively. Additionally, effects of various joint configurations, processing techniques, and strain on the transport property of the joint are also being studied.

INTRODUCTION

Considerable progress has been made in the development of high-critical-temperature (high- T_c) bismuth-strontium-calcium-copper-oxide (BSCCO) superconductors by the powder-in-tube (PIT) technique. Two important parameters, critical current density (J_c) and conductor length, have steadily improved since the first application of this technique to high- T_c materials. J_c values as high as $\approx 1.2 \times 10^4$ A/cm² have been obtained in a 125-m-long monocoil and an 850-m-long 37-filament conductor.¹⁻⁷

The long-length conductors have been fabricated into pancake-shaped coils, and high- T_c magnets have been assembled from them for use in applications such as motors, generators, and medical diagnostic equipments such as that used in magnetic resonance imaging.^{1-3,5,8} At present, resistive interconnections are used to join high-quality short- or medium-length conductors for coil winding and for interconnecting various parts of a superconducting device. Because the resultant Joule heating is undesirable, and the

Figure 1. Schematic representation of joint formation.

Figure 2. Longitudinal cross section of lap joint, illustrating three distinct joined, transition, and unjoined regions.

I_c as a function of heat-treatment time for the lap joint and normal tape is shown in Figure 5. Initially, I_c of the joined tape is low because of incomplete formation of the joint. After 250 h of thermomechanical treatment, typical I_c within and through the lap joint was 37 and 10 A, respectively. In comparison, I_c of a normal tape (heat treated simultaneously) was 31 A. The difference in I_c through and within the joint can be attributed to the difference in thickness between the joined and unjoined regions of the tape. During uniaxial pressing, the thickness difference causes nonuniform distribution of stresses. Because the joined region suffers more reduction than the unjoined region, the transition region between the two becomes sheared. Large transverse microcracks (Figure 6) are formed in the transition region. This in turn results in degradation of current transport through the joint.

Figure 6. SEM photomicrograph of lap joint showing microcracks in transition region.

Figure 7. SEM photomicrograph of butt joint after 250 h of heat treatment.

REFERENCES

1. K. Sato, T. Hikata, H. Mukai, M. Ueyama, N. Shibuta, T. Kato, T. Masuda, M. Nagata, K. Iwata, and T. Mitsui, *IEEE Trans. Magn.* 27:1231 (1991).
2. S. X. Dou, Y. C. Guo, J. Yau, and H. K. Liu, *Supercond. Sci. Technol.* 6:195 (1993).
3. U. Balachandran, A. N. Iyer, J. Y. Huang, R. Jammy, P. Haldar, J. G. Hoehn, Jr., G. Galinski, and L. R. Motowidlo, *J. Metals* 46:23 (1994).
4. U. Balachandran, A. N. Iyer, P. Haldar, J. G. Hoehn, Jr., L. R. Motowidlo and G. Galinski, *Appl. Supercond.* 2:251 (1994).
5. J. Schwartz, J. K. Heuer, K. C. Goretta, R. B. Poeppel, J. Guo and G. W. Raban, Jr., *Appl. Supercond.* 2:271 (1994).
6. M. Lelovic, P. Krishnaraj, N. G. Eror, and U. Balachandran, *Physica C* 242:246 (1995).
7. D. C. Larbaleister, X. Y. Cai, Y. Feng, H. Edelman, A. Umezawa, G. N. Riley, Jr., and W. L. Carter, *Physica C* 221:299 (1993).
8. J. W. Bray, *Appl. Supercond.* 2:149 (1994).
9. M. G. Benz, L. E. Rumaner, B. A. Knudsen, R. J. Zabala and H. R. Hart, *J. Mag. Matls.* 22:1299 (1993).
10. J. Cai, X. M. Xie, L. Baoshun, X. X. Huang, T. G. Chen and J. K. Guo, *Supercond. Sci. Technol.* 5:599 (1992).
11. M. A. Hilal, X. Huang and J. D. Lloyd, *IEEE Trans. Magn.* 27:927 (1991).
12. Y. Mutoh, M. Inoue and T. Konatsu, *Jpn. J. Appl. Phys.* 29:L1432 (1990).
13. J. E. Tkaczyk, R. H. Arendt, P. J. Bednarczyk, M. F. Garbaskas, B. A. Jones, R. J. Kilmer and K. W. Lay, *IEEE Trans. Appl. Supercond.* 3:946 (1993).
14. K. Shibutani, T. Egi, S. Hayashi, Y. Fukumoto, I. Shigaki, Y. Masuda, R. Ogawa and Y. Kawate, *IEEE, Trans. Appl. Supercond.* 3:935 (1993).
15. "CRC Handbook of Metal Etchants", P. Walker and W. H. Tarn, eds., CRC Press, Inc. Boca Raton, FL (1991).
16. G. F. Vander Voort, "Metallography Principles and Practice", A. Murphy and Susan Hazlett, eds., McGraw-Hill, New York, (1984).