RECEIVED

MAR 27 1996

CONF-960502--12

OSTI

ANL/CMT/CP--88893

**ELECTROCHEMICAL AND IN SITU NEUTRON
DIFFRACTION INVESTIGATIONS OF La-Ni-Al-H ALLOYS**

by

**W. Peng*, L. Redey, D. R. Vissers, K. M. Myles,
J. Carpenter, J. Richardson, and G. Burr
Argonne National Laboratory
Chemical Technology Division
Electrochemical Technology Program
9700 South Cass Avenue
Argonne, IL 60439**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

The submitted manuscript has been authored by a contractor of the U.S. Government under contract No. W-31-109-ENG-38. Accordingly, the U. S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U. S. Government purposes.

May 5-10, 1996

**To be presented at the Spring Meeting of The Electrochemical Society, Inc.,
Los Angeles, California May 5-10, 1996**

***Illinois Institute of Technology**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ELECTROCHEMICAL AND *IN SITU* NEUTRON DIFFRACTION INVESTIGATIONS OF La-Ni-Al-H ALLOYS

W. Peng*, L. Redey, D.R. Vissers, K. M. Myles
Electrochemical Technology Program

J. Carpenter, J. Richardson, and G. Burr
Intense Pulse Neutron Source

Argonne National Laboratory
9700 S. Cass Ave., Argonne, IL 60439

Introduction

The nickel/metal hydride (Ni/MH) battery is a strong contender to replace the nickel/cadmium battery because of its superior performance, low impedance, and absence of toxic cadmium. However, the present Ni/MH battery is limited by hydrogen management problems associated with charge/discharge operation and self-discharge of the battery and by long-term capacity loss due to corrosion of the MH electrode. Rare earth metal-based alloys such as LaNi_5 , preferably with the partial substitution of lanthanum or nickel by a small amount of other metal elements, seem to be promising MH materials to improve the stability and capacity of the MH electrodes. However, the role of alloying components is not yet clearly understood. Therefore, a combination of electrochemical and neutron diffraction techniques has been designed to investigate metal hydrides. This combination of the surface and bulk investigation techniques provides a unique tool to study the properties of the alloy electrodes *in situ* with respect to composition, atomic structure, and phase change [1-3].

In this work, several Al-substituted LaNi_5 alloys were investigated with respect to their specific capacity (measured by mAh/La and symbolized by x in $\text{LaNi}_{5-y}\text{Al}_y\text{H}_x$), impedance, and cycling stability. In addition to the extensive electrochemical investigations, *in situ* neutron diffraction measurements were performed to characterize the electrochemically induced phase transformation and structure change during charge and discharge of the metal hydride electrodes.

Experimental

The following simple cell reaction permits simple cell construction.

The electrochemical testing was carried out in a three-electrode cell consisting of a commercial $\text{NiO}(\text{OH})$ positive electrode, a Hg/HgO reference electrode with electrolyte bridge and Luggin capillary, a metal-hydride electrode, and 15% KOH electrolyte. Teflon mesh separator was used between the working and counter electrodes. The alloy powder (Rhône-Poulenc, -400 mesh size) was mixed with 5% carbon (Shawinigan Black) conducting additive and 10% DuPont Teflon 30 suspension and pressed onto an expanded nickel mesh to form 1-mm-thick electrodes.

To investigate the electrochemical performance of the metal hydride electrode, plane-parallel or jelly-roll electrode combinations were used to ensure uniform current density.

The following alloys in this study were investigated: LaNi_5 , $\text{LaNi}_{4.87}\text{Al}_{0.12}$, and $\text{LaNi}_{4.4}\text{Al}_{0.6}$. The electrochemical properties of the metal hydride electrodes, such as capacity, cell voltage, electrode potential, ASI_{30} , and cycle-life, were

investigated at room temperature and ambient (1 atm) pressure by interrupted galvanostatic cycling.

A different cell design was used for the *in situ* neutron diffraction measurements because the neutron diffraction measurements are adversely affected by the presence of protons. For these *in situ* experiments, a fully deuterated cell was designed:

To obtain a deuterated $\text{NiO}(\text{OD})$ electrode, two identical pieces of $\text{NiO}(\text{OH})$ electrodes removed from Ni/Cd cells were cycled in 15% KOD/ D_2O solution for 16-20 cycles. The electrolyte was exchanged every 4 cycles and analyzed by FTIR to determine the H/D ratio in the solution, which indicated the remaining proton content of the $\text{NiO}(\text{OD})$ electrode. A $\text{NiO}(\text{OD})$ electrode with an H/D ratio of less than 0.02 was accepted for the neutron diffraction measurements. The cell used in the *in situ* neutron diffraction measurements was constructed in a quartz tube (Fig. 1). The neutron diffraction patterns were recorded simultaneously with the electrochemical data. Neutron diffraction data from these operating cells comprise scattering from four components: the $\text{LaNi}_{5-y}\text{Al}_y\text{D}_x$ electrode, the Ni mesh support, the electrolyte and the quartz tube. With modern multi-phase analysis techniques, scattering from the electrolyte and quartz tube can be modelled as background, leaving only the crystalline Ni and $\text{LaNi}_{5-y}\text{Al}_y\text{D}_x$ phases to consider. Rietveld profile refinements provide precise data corresponding to phase identification, deuterium siting, and phase composition as a function of charge/discharge state.

Results and Discussion

The discharge capacity indicates the change in the value of x in the formula of metal hydride. Figure 2 shows plots of open-circuit cell voltage versus x for alloys of three different Al content. The open-circuit cell voltage was measured at the end of 150-second-long current interruptions. In Fig. 2, the data are shown for the fourth charge/discharge cycle. There are distinct differences in the capacities of the MH electrodes. LaNi_5H_x exhibited low specific capacity, while the Al-substituted alloys have dramatically increased cell capacity up to more than 10 times higher than that of the pure LaNi_5 parent alloy. It is evident from Fig. 2 that higher Al content of the alloy produces higher specific capacity. The low specific capacity of the LaNi_5 electrode at ambient pressure is mainly due to its inherent nature, which would require a high hydrogen pressure to achieve a higher x value [4]. The effect of higher Al concentrations on the cell performance improvement can be partly explained by the lowered hydrogen equilibrium pressure requirement of the Al-containing alloys [5]. This behavior can be assessed from the structure analysis of the neutron diffraction investigation.

Subtle crystallographic differences between electrodes containing Al and those without may provide insight into the mechanism. The presence of Al does influence the disposition of deuterium in the $\text{LaNi}_{5-y}\text{Al}_y\text{D}_x$ phases. Aluminum preferentially substitutes into one of three available crystallographic sites. When no aluminum is present, the maximum amount of deuterium that enters the alloys ($x < 0.5$) is limited to inclusion in the alpha phase. When deuterium is placed into an alloy containing aluminum, the amount of deuterium in the alpha phase remains constant, while the extra deuterium enters the beta phase. Results correlate with electrochemical measurements of x .

The stability of the selected hydride alloys was studied by electrochemical cycling. Figure 3 shows plots of specific capacity (as x value) of the three investigated alloy compositions versus the cycle number for cycles 1-20. The LaNi_5 electrode has low, but very stable, capacity. The $\text{LaNi}_{4.4}\text{Al}_{0.6}$ alloy electrode has the highest capacity ($x \leq 4.4$) with a relatively small drop. The alloy with a low concentration of Al, $\text{LaNi}_{4.87}\text{Al}_{0.12}$, however, has a rather poor stability indicated by a large capacity decay. One possible reason for this behavior is the selective dissolution of aluminum. Analysis of the electrolyte solutions from the cells indicated the presence of dissolved aluminum. Electrolytes from cells made with the $\text{LaNi}_{4.87}\text{Al}_{0.12}$ alloy contained 5 ppm Al after 12 cycles, 14 ppm after 29 cycles. Lanthanum was not detectable in these electrolytes. The higher concentration of Al in the $\text{LaNi}_{4.4}\text{Al}_{0.6}$ alloy, however, can compensate for the corrosion loss of Al for a longer time than in the case of the $\text{LaNi}_{4.87}\text{Al}_{0.12}$ alloy. Thus, electrodes with higher Al content have longer cycle life. These experiments show that the Al-alloying component is very important to produce a high specific capacity, but, also increases the sensitivity to corrosion. Surface modification of the alloy particles or introduction of other corrosion-suppressing alloying elements are necessary to achieve longer cycle life.

To explain the variation in electrochemical performance among the Al-containing alloys, the *in situ* neutron diffraction data were analyzed to gain insight on relationships between structural and electrochemical phenomena of these alloys. Preliminary results show correlations between electrochemical measurements and neutron diffraction refinements for endmember states.

Acknowledgment

This research was sponsored by the U.S. Army Research Office, Research Triangle Park, NC, through the ARO Fuel Cell / Battery Research Hub at the Illinois Institute of Technology. The research was conducted at Argonne National Laboratory, which is operated by the University of Chicago for the U.S. Department of Energy under Contract No. W-31-109-Eng-38.

References

1. L.Redey, K.M.Myles, F.J.Rotella, J.W.Richardson, G.P.Felcher, R.L.Hitterman, and R.Kleb, *Proceedings of the Symposium on Hydrogen Storage Materials, Batteries, and Electrochemistry*, Vol. 92-5, p. 258, Editors, D.A.Corrigan and S.Srinivasan, The Electrochemical Society, Pennington, NJ, (1992)
2. M. Latroche, A.Percheron-Guegan, Y.Chabre, C.Poinsignon, and J.Pannetier, *J. Alloys Comp.*, **189**, 59 (1992)
3. M.Latroche, J.Rodriguez-Carvajal, A.Percheron-Guegan, and F.Bouree-Vigneron, *J. Alloys Comp.*, **218**, 64 (1995)
4. H.F.Bittner and C.C.Badcock, *J. of Electrochem. Soc.*, **130**, 193c (1983)
5. E.D. Snijder, G.F.Versteeg, and W.P.M. van Swaaij, *J. Chem. Eng. Data.*, **39**, 405 (1994)

* Illinois Institute of Technology

Fig. 1 Schematic diagram of the electrochemical cell for *in situ* neutron diffraction measurements.

Fig. 2 Open-circuit voltage for $\text{MH}_x/\text{NiO}(\text{OH})$ cells as function of discharge capacity.

Fig. 3 Cycling behavior of the La-Ni-Al-H alloys for three aluminum composition.