CONF-960513--17

ENVIRONMENTAL ISSUES RELATED TO COMMERCIALIZATION OF CuInSe₂-BASED PHOTOVOLTAICS

Chris Eberspacher,* Vasilis M. Fthenakis,** and Paul D. Moskowitz**

*UNISUN, Newbury Park, CA 91320

**Biomedical and Environmental Assessment Group, Dept. of Applied Science
Brookhaven National Laboratory, Upton, NY 11973

RECEIVED

JUL 15 1986

OSTI

ABSTRACT

One of the most promising materials for low-cost thin film photovoltaic cells is copper indium selenide (CuInSe₂ or CIS). As with any new material, successful commercialization of CIS photovoltaic (PV) technology will require attention to environmental issues related to the sources of raw materials, their usage, and the disposal and/or recycling of products at the end of their useful life. This paper focuses on three specific environmental issues related to CIS technology: (i) Economics of the use and re-use of materials; (ii) regulations on environmental disposal and waste handling, and (iii) logistics and economics of recycling and disposing of products by industries faced with comparable environmental issues.

COST AND MATERIAL AVAILABILITY OF CIS PV

Estimates of the production costs for large scale (i.e., 10-20 MW/yr) CIS PV modules range from \$0.5-1.5/W. The materials in CIS modules cost 35-45% of the total projected manufacturing costs. Glass for the substrates and cover sheets accounts for about one third of this amount, and the active thin-film electrodes and semiconductor junction materials account for an additional one quarter to one third. Indium is the most costly of the thin-film constituents, accounting for 2.5-5% of the total projected cost of a module. The absence of any key recoverable material makes it unlikely that the availability of materials will economically warrant recovering any materials from worn-out modules.

Overall material supply is an important issue for the long-term contribution of CIS PV technology. In the long-term, large-scale production of CIS PV modules may be limited by the availability of indium and selenium to levels of ca. 200 GWp. Furthermore, other new and growing industries may compete with the PV industry for these materials; for example, the flat-panel display industry may compete for In. These reasons suggest that we should consider options for minimizing the consumption of these materials, and for recovering these materials from end-of-life modules.

ENVIRONMENTAL REGULATIONS

Federal and State environmental regulations can have a significant impact on product manufacturing, use, and disposal, and recycling. Applicable regulations are the Resource Conservation and Recovery Act (RCRA), its various amendments, and corollary State regulations.

The RCRA relates only to solid wastes and defines them as any "discarded material" that is not specifically excluded. Neither PVs in general, nor CIS in particular, are excluded from the general definition of a solid waste. CIS materials and CIS PV modules are not an "inherently waste-like" material according to RCRA definitions, but end-of-life CIS PV modules are likely to be categorized as solid wastes unless handled in a manner that qualifies for exclusion. Unused defective PV modules and various manufacturing by-products (e.g. broken module plates, patterning dusts) might be exempted from being handled as a solid waste if sent for reclamation. RCRA assigns a hazard classification to wastes based on four characteristics: ignitability, corrosivity, reactivity, and toxicity. The California Hazardous Waste Control Law (HWCL) incorporates RCRA and expands the toxicity requirements by adding additional criteria of total concentration to the toxicity characteristic.

Under RCRA regulations, CIS PV modules (not excluded from classification by the reclaim provisions of the solid-waste definition) are likely to be classified as non-hazardous provided the modules do not exhibit hazardous "characteristics". Under HWCL regulations, CIS PV modules would likely be classified as non-hazardous if the Toxic Characteristic Leaching Procedure (TCLP) and the Soluble Limit Concentration (STLC) tests were "passed", except that current CIS PV structures probably will exceed the TTLC limits for total concentrations of selenium.

The RCRA contains additional provisions of key importance in determining how a material is to be handled; they concern recycling, small quantity generators, household wastes, and when a product becomes a waste. The impact of these provisions is that used CIS PV modules could be handled as non-hazardous waste if sent for recycling as an ingredient in or as a substitute. This allows used modules to be

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

recycled e.g., by metal smelters who use the substrate and cover glass as sources of silica for their slagging material.

LOGISTICS AND ECONOMICS OF RECYCLING AND DISPOSING OF CIS PVS

The logistics and economics of CIS PV recycling and disposal were examined from three points of view [1]: (1) a zero-order estimate was made of recycling economics, based solely on materials economics; (2) the prospects and pitfalls of recycling similar products were examined by a survey of comparable industries; (3) the regulatory framework, materials economics, and the experiences of comparable industries were synthesized into recommendations for a workable recycling program for PV modules.

Materials Economics

It is unlikely that CIS PV modules can be economically recycled for the value of their materials. The highest salvage value of a CIS PV module is likely to be from the silica content of the glass. Metals smelters, who purchase silica for slagging, may be willing to recycle PV modules, though the sodium and calcium content of the glass typically used in PV modules lessens their economic value as a slagging material. Metals in the module will be effectively consumed since, for example, the copper content of a CIS PV module (0.2 wt%) is less than the average copper content in slag (0.5-0.8 wt%).

Comparable Industries

The electronics and telecommunications industries are among those concerned with environmental issues similar to those of the photovoltaic industry. They were discussed in detail elsewhere [2,3,4]. To put the discussion of comparable industries in context, the average materials content of PV modules, electronic goods and appliances can be compared. Thin-film CIS PV modules are dominated by their glass content, whereas printed circuit boards, computers, and telephones are dominated by metals, plastics, and fiberglass. These differences in materials content can have an important impact on recycling techniques and economics.

The experiences and practices of the industries of printed circuit boards, electronics, telecommunications, and fluorescence light tubes were described elsewhere [3]. From these experiences, we conclude that unused defective CIS PV plates and modules are likely to be "unlisted commercial chemical products" which are not solid wastes when sent for reclamation. Similarly, debris and dusts generated during the manufacturing of modules are likely to be "unlisted by-products" which are not solid wastes when reclaimed. Thus, provided a reasonably cost-effective procedure for reclamation is available, CIS PV plates, modules, and manufacturing by-products probably will not

require handling as hazardous wastes, independent of their TCLP test results.

The electronics and telecommunications industry recycles a wide range of used and unused products through a plethora of collection and processing channels. Used computers and telephones typically are collected, consolidated, and shipped to a "service center". The used items are regarded as used products, not wastes, during these first steps in the recycling sequence. The service center does one of three things: (1) refurbishes the used equipment for resale as a working unit, (2) disassembles the unit for spare parts, or (3) dismantles the unit to reclaim the materials. Refurbished units and spare parts remain "products", while units and/or pieces sent for reclaiming are "wastes" (subject to RCRA). The economics of recycling electronics and telecommunications is driven by the value of the usable components salvaged from recycled units and by their precious metals content.

Paralleling these practices, collecting and consolidating used PV modules would be greatly simplified if used modules were returned to the manufacturer or a contracted recycling center as "products" destined for potential refurbishment as PV modules. A manufacturer or refurbisher could evaluate used modules for repair, disassembly, or dismantling for reclaiming without necessarily triggering waste treatment regulations.

The key to recycling glass is to separate the glass, plastic, metals, and paper, and a wide variety of innovative processes and machines are used to do this. Unfortunately, glass-containing products that are close corollaries to laminated PV modules are seldom cost-effective to recycle at present. For example, laminated front auto-windshields generally are not recycled because the laminate plastic is difficult to remove and hinders the grinding of cullet to the manufacturer's specifications. PV modules probably will be difficult to recycle via glass recycling channels due to their metals content and similar difficulties in grinding. However, by using a non-laminated PV-module package (e.g. glass/glass edge-sealed package), then it might be possible to separate the glass and films sufficiently to recycle the glass through existing glass recycling channels, and the films through existing metals-recycling channels. On the other hand, large primary and secondary metal smelters are able to cost-effectively process lower concentration metal sources, and they are interested in working with PV module manufacturers to recycle thin-film PV modules.

WORKABLE RECYCLING

A feasible recycling program for PV modules will require careful attention to the regulatory framework, material economics, and the experiences of comparable industries. The basic viability of any recycling program often hinges on concentration:

- Geographic concentration of the goods and their proximity to appropriate recycling facilities;

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

- Functional concentration in the steps of a recycling sequence, (e.g. decommissioning, dismounting, collecting, consolidating, pre-processing, transporting and recycling);
- Content concentration of valuable materials in the goods to be recycled.

Thin-film photovoltaics is not at present very concentrated - not by geography, by function, or by content. Present markets for PV are dominated by geographically dispersed installations, such as off-grid power systems for industrial sites, and stand-alone residential applications. The average PV system is small compared to a minimum transportation load of reclaimed material accepted by smelters, e.g. 1-2 kW vs. 35-40 kW which is necessary to meet a 10,000 lb minimum. The regulatory framework and legal liability concerns are likely to segment the PV module recycling sequence. The total amount, concentration, and value of the content of reclaimable material is low. The materials reclaim value probably will be less than costs of collection and processing. At best, recycling PV modules will be a challenge.

Reaven [4] proposed three generic paradigms (i.e., utilities, electronics and batteries) for institutional infrastructure to address the challenges inherent in recycling PV modules. In the utilities paradigm, large end-users (e.g. electric utilities) would be the primary owners and/or servicers of large PV systems; hence, utilities logically would be primarily responsible for collecting and transporting the end-of-life modules to the recyclers. PV module recycling would be integrated with other utility programs, such as conservation, off-grid service tariffs, and demand side management. Recycling charges would be imbedded in the rates charged by the utility.

In the electronics model, recycling of PV modules would mimic the recycling of electronics and telecommunications products. Manufacturers would be individually responsible for collecting and transporting end-of-life modules to the recyclers. Collection, consolidation, and transport would likely involve reverse logistics companies, and recycling would be done by integrated dismantlers (i.e. not exclusive to PV modules) and materials recyclers. Recycling services might be paid for by the generator, the manufacturer, or by some kind of escrow fund set aside when the PV systems were purchased.

In the batteries paradigm, manufacturers would be collectively responsible for collection and transport to recyclers, probably through the incorporation of a collectively supported PV-module recycling entity. Reverse retail channels and consolidation entities would probably be responsible for collection, consolidation, and transport; and the modules recycled by dedicated dismantlers, and materials recyclers. Goods collected through reverse retail channels could be transported directly to smelters under pre-paid shipping arrangements. Consolidation entities could collect goods from municipal recycling centers and large commercial and institutional generators. Recy-

cling services might be paid for by industry dues to the collective recycling entity.

While these generic paradigms are useful in identifying elements of recycling programs that might be workable for PV modules, none of those fits all the potential needs of the photovoltaics industry. Instead, a program that includes parts of the above paradigms may be workable in the PV industry. In this context, four general observations are made:

(1) Paralleling the utility paradigm, collecting decommissioned PV modules is probably feasible for large, centralized installations. The costs of recycling large systems can be absorbed by the system's installer or capitalized by the system's owner.

(2) Collecting dispersed modules in small, remote installations and consumer applications will be problematic. Paralleling the battery paradigm, reverse retail channels and periodic pick-up by reverse logistics companies may be the best strategy. With the market segmentation and materials dispersion of PV products, collective action by PV module manufacturers is essential, but competitive pressures and lack of regulatory imperatives reduce the prospects for this happening.

(3) Recycling modules collected by municipal entities should likely be handled by the PV industry with an arms-length information role. Municipalities may separate end-of-life PV modules from other municipal solid waste, particularly if they are classified as a hazardous waste under Federal, State, or local regulations. The PV industry could provide guidance for municipalities, without assuming the legal liability of getting directly involved with the handling and recycling of these materials.

(4) Multi-materials recyclers, such as those entities active in recycling electronics and telecommunications equipment, may be useful participants in recycling efforts for PV modules even if they do not provide the reclaim values of salvaging components and precious metals that normally support recycling in those fields. These multi-materials recyclers have a wide spectrum of process expertise that might accommodate PV module recycling in the future.

The actual recycling of CIS PV modules probably will proceed along four technological steps.

The projected economics of recycling CIS PV modules can be estimated from the information gathered from comparable industries and existing recycling programs. Three cases were examined [5]: First, a base case assuming that dispersed, low-concentration PV modules were recycled via reverse retail and/or curbside municipal solid waste channels. In this base case, an incentive paid to the generator or primary collector of \$1/module might be necessary. The net of this scenario would be a recycling cost of about 8¢/W. An alternate best-case recycling scenario would assume that no incentive was paid to the generator or primary collector and there was a Net Present Value credit of about 5¢/W for avoiding future environmental liability if disposed of instead of recycled. The net of this best-case scenario is roughly break-even.

Generator-based recycling via direct transport by the small generator to the recycler would entail higher transportation costs (due to smaller shipment loads) and higher recycling costs (due to smaller processing loads). Large generators (e.g. utilities) would garner the lower rates possible with larger shipments and processing loads, and be able to roughly balance recycling costs against avoiding future liability in order to break-even.

CONCLUSIONS

Successful commercialization of CIS PV technology will require attention to environmental issues, including supplies of source materials and disposal or recycling of end-of-life products.

Indium and selenium reserves may place an ultimate upper limit on the production of CIS PV products.

PV modules and module manufacturing by-products and wastes are regulated under RCRA and under comparable State regulations. Under RCRA regulations, CIS PV modules may be classified as non-hazardous provided they do not exhibit toxicity characteristics. This requires that the selenium-containing compounds be insoluble, and that certain design restrictions apply (e.g., the CdS film is thin and only on one side, and lead-free solder is used).

Under California regulations, CIS PV modules would likely be classified as non-hazardous except for exceeding the Total Threshold Limit Concentration (TTLC) for selenium. The CIS PV industry can address the Se TTLC issue via legislative, re-classification, or rule-making processes.

Unused defective CIS plates are likely to be exempt from RCRA regulation if reclaimed as an unlisted commercial chemical product. Various processing byproducts (e.g. flakes, dusts) probably will be RCRA-exempt if reclaimed as unlisted by-products.

The economics of recycling of CIS PV materials will hinge on exemptions in Federal and California State regulations for solid wastes recycled as an ingredient in a industrial process, or as a safe and effective substitute for commercial products. In particular, metals smelters may use thin-film PV plates and modules as viable sources of silica for slagging. Regulations allowing "pre-treatment" of wastes before their use or re-use will be important in facilitating economic recycling. The highest salvage value of a CIS PV module is likely to be that of the silica content of the glass used in slagging by metals smelters.

A workable recycling program for PV modules will require careful attention to the regulatory framework, materials economics, and the experiences of comparable industries. Paralleling the practices of the electronics and telecommunications industries, collecting and consolidating used PV modules would be greatly simplified if used modules are returned to the manufacturer or a contracted recycling center as "products" destined for potential refurbishment as PV modules. A manufacturer or refurbisher could evaluate used modules for repair, disassembly, or dismantling for

reclaim without necessarily triggering RCRA waste treatment regulations.

Separating materials and subsequently concentrating them are essential aspects of recycling. PV modules will be difficult to recycle via glass-recycling channels due to their content of metals and the difficulty in grinding the laminate to cullet specifications. However, if a non-laminated PV module package was used, then it might be possible to separate the glass and films sufficiently to recycle the glass through existing glass-recycling channels and the films through existing metals-recycling channels. Further work on techniques for disassembling PV modules will be important in quantifying whether modules can be cost-effectively disassembled for materials reclaim, or whether the focus must remain on recycling the unseparated module (e.g. shredded and fed into a metals smelter).

REFERENCES

- [1] Eberspacher, C., Fthenakis, V. M. and Moskowitz, P. D. *Environmental, Health and Safety Issues Related To Commercializing CuInSe₂-Based Photovoltaics*. BNL Informal Report (in press).
- [2] Reaven, S. J. *Recycling and Waste Minimization Prospects for Photovoltaic Modules: A Preliminary Assessment*. Prepared for Brookhaven National Laboratory, August 1994 (unpublished).
- [3] Eberspacher, C. et al. *Thin-Film Photovoltaic Manufacturing Technology, Tutorial, First World Conference on Photovoltaic Energy Conversion*, Waikoloa, 1994 (unpublished).
- [4] Reaven, S. J. , Moskowitz, P. D., and Fthenakis, V. M. *Model Institutional Infrastructures for Recycling of Photovoltaic Modules*. BNL 62837, January 1996.
- [5] Eberspacher, C., Gay, C. F., and Moskowitz, P. D. *Strategies for Enhancing the Commercial Viability of CdTe-Based Photovoltaics*. BNL Informal Report (in press).