Chemistry of Mercury Species and Their Control in Coal Combustion

**Semi-Annual Report
March 1 - August 31, 1997**

Work Performed Under Contract No.: DE-FG22-95PC95222

For
U.S. Department of Energy
Office of Fossil Energy
Federal Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880

By
Aerosol and Air Quality Research Laboratory
Department of Civil and Environment Engineering
University of Cincinnati
Cincinnati, Ohio

Disclaimer

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

CHEMISTRY OF MERCURY SPECIES AND THEIR CONTROL IN COAL COMBUSTION

DOE Grant Agreement No. DE-FG22-95PC95222--06

Aerosol and Air Quality Research Laboratory
Department of Civil and Environment Engineering
University of Cincinnati

Reporting Period: March 1997 - August 1997

Date of Report: August 30 1997

Grant Date: August 1, 1995

Anticipated Completion Date: July 31, 1998

Program Manager: Diane Revay Madden
Principal Investigator: Pratim Biswas
Contracting Officer's Representative: Cynthia Weitlauf

OBJECTIVES

The objectives for this reporting period are:

- 1) The study of mercury capture mechanism by using titania sorbent and ultraviolet (UV) light, and the study of structural difference between titania particle generated by both thermal Oxidation at 1000°C and by reacting with water vapor at room temperature.
- 2) Measurement of ultra-fine particle size distribution in flue gas after burning coal.

SUMMARY OF TECHNICAL PROGRESS

Effect of UV Light on the Capture of Hg using Titanium Based Vapor Phase Sorbent Precursors

The experiments initiated in the earlier project period were completed, and the results were promising with very high capture efficiencies for Hg. The methodology is promising because it could potentially rely on the UV irradiation present in Electrostatic Precipitators. The titania sorbent has been shown to be 100 times more effective than activated carbon. Low ratios of sorbent to metal are required, and the precursor is not very expensive, thus the metals capture methodology is also cost effective.

The results have been summarized as a Journal Publication (please see Appendix I). A Patent Application has also been filed for the process.

Structural Studies of the TiO₂ Agglomerates

In the previous quarter, the in situ generated agglomerated silica sorbents were characterized by real time size distribution measurements and on line light scattering measurements. The surface area evolution of the sorbent is an important parameter, and this quarter, the titania sorbents were characterized. As a preliminary study on the other vapor phase sorbent precursors, we conducted experiments to investigate the structural characteristics of the TiO₂ agglomerates generated at high temperatures under diffusion-limited conditions. Also, the size distribution of the TiO₂ particles generated by reacting with water vapor at room temperature was measured to study the structural differences between titania particles generated by both thermal oxidation at 1000 C and by reacting with water vapor at room temperature. The measured size distribution shows that the mean size of the particle generated in the latter case is much smaller than that of the particle generated in first case. The geometric mean size of the TiO₂ generated by reacting

with water vapor is 115 nm while that of the titania agglomerates from thermal oxidation is 250 nm. The number density of the latter case is $9.2\text{E}+6$ [#/cc], while that of the first case is $5.8\text{E}+5$ [#/cc]. These indicate that due to the lower rate of sintering and coagulation at room temperature resulted in smaller size and larger number density. The TEM pictures of the TiO_2 particles from both cases will be taken to measure the primary particle size and the number of primary particles in each agglomerate.

Figures 1 and 2 show the measured size distributions for the cases of thermal oxidation of Ti precursor, Ti precursor with water vapor at 100 cc/min, respectively. As shown in the figures, for the case of Ti precursor reacting with water vapor resulted in smaller mean size and larger number concentration than that for the case of thermal oxidation of Ti precursor. These indicate that due to the lower temperature, rates of sintering and the coagulation are lower than that in the thermal oxidation case, which results in a smaller mean size and larger number concentration and consequently, larger surface area. The x-ray diffraction pattern however indicated that the high temperature oxide has a greater fraction of the anatase phase, thus it was photochemically more reactive.

Coal Combustion Experiment

A laboratory scale experimental system was setup to characterize the aerosol produced during pulverized coal combustion. The schematic diagram of the system is shown in Figure 3. The emphasis in this work has been on the ultra-fine particulate matter present in the flue gas. The pulverized coal powders (around 40-60 μm) flow into the vertical tubular furnace, which is maintained at 1000 C. The combustion products then pass through a MARK-III cascade impactor (last stage cutoff diameter = 0.46 μm) to separate the large particle from the flue gas. The CPC (Condensed Particle Counter) measurement indicates that total number concentration of ultra-fine particle (in the range between 30 nm to 800nm) is very high, in the magnitude of 10^6 #/cc. The preliminary data (dilution ratio = 50) is plotted in Figure 4. The fluctuation of the data can be ascribed to the characteristics of the system. A SMPS (Scanning Mobility Particle Sizer) system is used for size distribution measurements. The experimental data are shown in Figure 5. It is noted there exist a peak around 100 nm particle diameter.

The system will be used to characterize the trace metal constituent with an emphasis on the speciation of mercury and distribution amongst various sizes.

PUBLICATIONS

- 1) Study of Gas Phase Reactions, Aerosol Formation and Growth Dynamics of Toxic Metals at High Temperatures”, Ph.D. Thesis, Chang-Yu Wu, Aerosol and Air Quality Research Laboratory, University of Cincinnati, December 1996.

- 2) P.Biswas and C.Y.Wu, "Enhanced Capture of Heavy Metal Emissions" Patent Filed, May 1997.
- 3) C.Y.Wu, T.G.Lee, E.Arar, G.Tyree, P.Biswas, "Capture of Hg from Combustion System By In-Situ Generated Titania Particle with UV-Irradiation", submitted to Combustion Science & Technology, June, 1997.
- 4) C.Y.Wu, T.G.Lee, E.Arar, P.Biswas, "Novel In Situ Generated Sorbent Methodology and UV Irradiation for Capture of Mercury in Combustion Environments", EPRI-DOE-EPA Combined Utility Air Pollutant Control Symposium, Particles and Air Toxics, Aug. 25-29, 1997, Washington D.C.

WORK TO BE PERFORMED OVER NEXT REPORTING PERIOD

During the next period, the following experiments will be performed:

- 1) The flow reactor experiments will continue over the next reporting period. The objective is to complete the structural studies of SiO_2 agglomerates and TiO_2 agglomerates. Experiment will also be conducted with the other sorbents (Si and Ca) for mercury capture with/without UV light.
- 2) The pulverized coal powders will be burned under variable working condition, and ultra-fine particle size distribution measurement will also be made. The elemental composition of trace species will also be determined as a function of particle size.
- 3) A system to test the capture of toxic species when coal is combusted will be designed.

Figure 1. Size distribution of TiO₂ generated from thermal oxidation of Ti precursor at 1000 °C.

TiO₂ Size Distribution
Ti Precursor Reacting with Water Vapor at Room Temperature

Figure 2. Size distribution of TiO₂ generated from oxidation of Ti precursor by reacting with water vapor at room temperature.

Figure 3 Coal Combustion Experimental System

**Figure 4. The variation of total concentration with time
(dilution ratio = 50)**

**Figure 5. Particle Size Distribution Combusting Ohio 5 Coal
(dilution ratio = 50; Sample after impactor)**