DIRECT AROMATIZATION OF METHANE
QUARTERLY TECHNICAL PROGRESS REPORT No. 12

Prepared for the US Department of Energy Under

Contract No. DE-AC22-92PC92109

by

ALTAMIRA INSTRUMENTS

149 Delta Drive

Pittsburgh, PA 15238

Date of Report: November 9, 1995
Date of Contract: September 28, 1992
Anticipated Completion: November 27, 1995
Total Government Award: \$340,930
Program Manager: George Marcelin
Reporting Period: 7-01-95 to 9-30-95

RECEIVED
USDOE/PETC
55 NOV 13 AM 10:52
ACQUISITION & ASSISTANCE DIV.

MASTER

TABLE OF CONTENTS

Executive Summary	i
Objective	1
Technical Report	1
Introduction	1
Experimental	2
Results and Discussion	3
Current Status	4
Work Planned for the Next Quarter	4

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LIST OF TABLES

Table 1.	BET Surface Areas of Catalysts Studied	5
Table 2.	Summary of Qualified Experimental Runs Performed During Reporting Period	6

LIST OF FIGURES

Figure 1:	Methane Conversion During Catalytic Pyrolysis of Methane in the Absence and Presence of Ethane at 1050 °C	11
Figure 2:	Typical Product Distribution During Catalytic Pyrolysis of Methane at 1050 °C	12
Figure 3:	Product Distribution During Catalytic Pyrolysis of Methane in the Presence of Ethane at 1050 °C	13

EXECUTIVE SUMMARY

Further investigations of the initiation of pyrolysis by a solid surface using a variety of catalysts with different surface areas and compositions were carried out during this reporting period. The effects of catalyst surface area, reaction temperature, and presence of ethane have been addressed. In general, catalysts such as α -Al₂O₃, SiC, or hexaaluminates were found able to lower the reaction temperature but led to increased "tar" formation. The addition of ethane increased further the conversion at the higher temperatures and lowered the amount of "tar". There appears to be no correlation between catalytic surface area and activity/selectivity for methane conversion.

OBJECTIVE

The thermal decomposition of methane shows significant potential as a process for the production of higher unsaturated and aromatic hydrocarbons when the extent of the reaction is limited. Preliminary experiments have shown that cooling the products and reacting gases as the reaction proceeds can significantly reduce or eliminate the formation of solid carbon and heavier ($C_{10}+$) materials. Much work remains in optimizing the quenching process and this is one of the goals of this program. We will also study means to lower the temperature of the reaction as this will result in a more feasible commercial process due to savings realized in energy and material construction costs. The use of free-radical generators and catalysts will be investigated as a means of lowering the reaction temperature thus allowing faster quenching. It is highly likely that such studies will lead to a successful direct methane to higher hydrocarbon process.

TECHNICAL REPORT

INTRODUCTION

During the twelve quarter of this project we have focused on the investigation of the initiation of pyrolysis by a solid surface using a variety of catalysts. Thermally stable and chemically inert (which will not be reduced by methane at elevated temperature) catalysts which could maintain reasonable surface area at high temperature ($>1100\text{ }^{\circ}\text{C}$) were chosen for these studies. The latter were carried out in the modified system consisting an unquenched shorter reactor and furnace described in the previous quarterly report. The effect of catalyst surface area, reaction temperature,

and presence of ethane have been addressed.

EXPERIMENTAL

Catalytic Pyrolysis

The catalysts used included two low surface area solids, i.e., SiC and α -Al₂O₃, and a series hexaaluminates with various surface areas and compositions. These catalysts were selected on the basis of their moderate surface area and structural stability at the temperature of interest, up to 1200°C. Moreover, they were relatively inert to reduction during the methane pyrolysis step. The BET surface areas of these catalysts were measured after calcination at 1200 °C or higher and the results are shown in Table 1.

Catalytic pyrolysis was carried out at temperatures between 850 and 1100°C. Methane flow rate of 200 Scc/min and 0.5 g of catalyst were used. The addition of a free radical initiator during catalytic pyrolysis was also studied with an ethane flow rate maintained at 6.2 Scc/min. All the catalysts were calcined *in-situ* under flowing air at 1100°C for approximately 16 hours. Following pretreatment, the catalyst samples were brought to reaction temperature under nitrogen flow. The flow was then switched to methane or methane/ethane and a GC sample was withdrawn after 1.5 min of reaction. In subsequent runs the coke was burned off from the catalyst surface by flowing air over it for 30 min at 700°C. This practice has ensured that coke free catalyst surface was maintained for subsequent reactions carried out at different temperatures.

RESULTS AND DISCUSSION

Table 2 summarizes the methane pyrolysis results obtained with the different catalysts at different temperatures without and with ethane addition. The results obtained with most catalysts without ethane addition indicate significant methane conversions at temperatures as low as 950 °C. However, the selectivity towards "tar" was significant under the conditions used. The "tar" selectivity decreased with increasing temperature, thus indicating a shift from a surface initiated pyrolysis at the lower temperatures towards gas phase pyrolysis at the higher temperatures.

Methane conversions during catalytic pyrolysis in the presence and absence of ethane at 1050°C are compared in Figure 1. Typically, the addition of ethane increased further the conversion at all temperatures and lowered the amount of "tar" except at the lowest temperature (950 °C) where methane conversion was higher without ethane addition in all cases. The higher reactivity of ethane which would result in a faster coke buildup on the catalyst may explain the lower activity at the low temperature in the presence of ethane. Such results confirms that the pyrolysis reaction at low temperature was occurring on the catalyst surface or at least that it was initiated on the catalyst surface. In addition, there appears to be no correlation between catalytic surface area and activity for methane conversion even at the lowest temperature where most of the reaction is believed to be catalytic. At the high temperature most of the methane conversion observed may be attributed to gas phase pyrolysis. At the lower temperatures, it is suspected that the high catalyst activity for methane pyrolysis may have resulted in the high selectivities for "tar" as well as in a fast carbon buildup on the catalyst surface. Thus, further reaction, if any, would occur on the carbon layer for all the catalysts. This would explain the similarity between all the catalysts. Further studies of the effect of carbon buildup on the catalyst surface planned for the next period may provide a better

explanation.

Typical product distributions obtained with and without catalyst during catalytic pyrolysis of methane in the absence and presence of ethane are shown for the reaction at 1050 °C in Figures 2 and 3, respectively. As with activity for methane conversion, there appears to be no correlation between catalytic surface area and product selectivity.

CURRENT STATUS

The project is within schedule and running within the proposed costs.

WORK PLANNED FOR THE NEXT QUARTER

In the next quarter, we expect to complete the overall study by concluding the experimental work on the initiation of pyrolysis by a solid surface. The effect of carbon buildup with time-on-stream on the catalyst surface will be addressed. The rest of the period will be dedicated to writing the final report.

Table 1. BET Surface Areas of Catalysts Studied

Catalyst	BET Surface Area (m ² /g)
α -Al ₂ O ₃	ca. 1
SiC	<1
BaMnAl ₁₁ O _{19-α}	5
LaMnAl ₁₁ O _{19-α}	34
La _{0.25} Sr _{0.75} Al ₁₁ O _{19-α}	12

Table 2

Summary of Qualified Experimental Runs Performed During Reporting Period

Run No.	Temp. (°C)	Catalyst ^a	Methane		Ethane		Carbon Selectivities (%)			
			Flow (ml/min)	Conv. (%)	Flow (ml/min)	Conv. (%)	C ₂	Aromt	C ₂ -C ₁₀	"Tar"
118-1	850	α -Al ₂ O ₃	200	0	0	-	0	0	0	0
120-1	950	"	"	4.5	"	-	1.7	0	8.7	91.4
120-2	1050	"	"	8.5	"	-	6.7	0.2	14.1	85.9
121-1	"	"	"	6.6	"	-	6.6	4.5	14.8	85.2
121-3	"	"	"	6.1	"	-	10.3	0.6	22.2	77.8
120-3	1100	"	"	17.8	"	-	4.2	0.4	11.8	88.2
120-4	"	"	"	16.9	"	-	11.6	4.9	19.9	80.1
118-5	850	"	200	<1	6.2	?	x	x	x	x
120-5	"	"	"	12.3	"	97.8	13.9	13.1	31.8	68.2
120-6	1100	"	"	25.8	"	99.3	11.7	14.2	28.4	71.6

(a) approx. 0.5 gm of catalyst used

(x) could not be analyzed accurately

Table 2 (contd.)

Summary of Qualified Experimental Runs Performed During Reporting Period

Run No.	Temp. (°C)	Catalyst ^a	Methane		Ethane		Carbon Selectivities (%)			
			Flow (ml/min)	Conv. (%)	Flow (ml/min)	Conv. (%)	C ₂	Aromt	C ₂ -C ₁₀	"Tar"
124-1	950	SiC	200	<1	0	-	x	x	x	x
124-2	1050	"	"	3.6	"	-	5.0	1.5	24.3	75.7
124-3	1100	"	"	11.6	"	-	33.3	18.3	63.7	36.3
124-4	950	"	"	1.3	6.2	91.1	53.8	1.6	77.6	22.4
124-5	1050	"	"	11.1	"	97.0	29.8	18.0	57.9	42.1
124-6	1100	"	"	25.8	"	98.6	24.7	24.5	55.5	44.5

(a) approx. 0.5 gm of catalyst used

(x) could not be analyzed accurately

Table 2 (contd.)

Summary of Qualified Experimental Runs Performed During Reporting Period

Run No.	Temp. (°C)	Catalyst ^a	Methane		Ethane		Carbon Selectivities (%)			
			Flow (ml/min)	Conv. (%)	Flow (ml/min)	Conv. (%)	C ₂	Aromt	C ₂ -C ₁₀	"Tar"
123-1	950	BaMnAl ₁₁ O ₁₉	200	2.3	0	-	x	x	x	x
123-2	1050	"	"	3.9	"	-	1.0	0.0	10.0	90.0
123-3	1100	"	"	11.6	"	-	15.6	9.4	37.3	62.7
123-4	950	"	"	1.7	6.2	79.0	48.1	1.0	69.9	31.1
123-6	1050	"	"	8.1	"	90.2	27.2	21.0	60.2	39.8
123-5	1100	"	"	19.6	"	93.4	14.8	21.1	41.3	58.7

(a) approx. 0.5 gm of catalyst used

(x) could not be analyzed accurately

Table 2 (contd.)

Summary of Qualified Experimental Runs Performed During Reporting Period

Run No.	Temp. (°C)	Catalyst ^a	Methane		Ethane		Carbon Selectivities (%)			
			Flow (ml/min)	Conv. (%)	Flow (ml/min)	Conv. (%)	C ₂	Aromt	C ₂ -C ₁₀	"Tar"
123-1	950	LaMnAl ₁₁ O ₁₉	200	3.2	0	-	-	-	15.4	85.6
123-2	1050	"	"	6.5	"	-	7.1	3.1	21.5	78.5
123-3	1100	"	"	25.5	"	-	10.9	8.9	22.0	78.0

(a) approx. 0.5 gm of catalyst used

(x) could not be analyzed accurately

Table 2 (contd.)

Summary of Qualified Experimental Runs Performed During Reporting Period

Run No.	Temp (°C)	Catalyst ^a	Methane		Ethane		Carbon Selectivities (%)			
			Flow (ml/min)	Conv. (%)	Flow (ml/min)	Conv. (%)	C ₂	Aromt	C ₂ -C ₁₀	"Tar"
126-1	950	La _{0.25} Sr _{0.75} Al ₁₁ O ₁₉	200	3.6	0	-	0.1	0.6	9.5	90.5
126-2	1050	"	"	7.3	"	-	9.9	0.3	16.7	83.3
126-3	1100	"	"	11.5	"	-	34.1	12.4	58.7	41.3
126-4	950	"	"	2.9	6.2	80.8	40.9	1.0	55.5	44.5
126-5	1050	"	"	8.4	"	92.3	24.7	17.4	53.1	46.9
126-6	1100	"	"	19.1	"	100.0	21.5	15.0	40.9	59.1

(a) approx. 0.5 gm of catalyst used

Figure 1. Methane Conversion During Catalytic Pyrolysis of Methane in the Absence and in Presence of Ethane at 1050°C

Figure 2. Typical Product Distribution During Catalytic Pyrolysis of Methane at 1050°C

Figure 3. Product Distribution During Catalytic Pyrolysis of Methane in the Presence of Ethane at 1050°C