Note: This is a preprint of a paper submitted for publication. Contents of this paper should not be quoted or referred to without permission of the author(s).

Submitted for publication in *Proceedings of EMAG 95* (Electron Microscopy and Analysis Group), Birmingham, UK, September 12-15, 1995,
published by the Institute of Physics

Microanalysis at the Atomic Level

S. J. Pennycook, D. E. Jesson, M. M. McGibbon,* A. J. McGibbon,*
P. D. Nellist, and N. D. Browning[†]

Solid State Division

Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831-6030

*Dept. of Physics & Astronomy, University of Glasgow, Glasgow G12 8QQ Scotland

[†]University of Illinois at Chicago, Chicago, Illinois 60607-7059

RECEIVED

FEB 05 1996

OSTI

"The submitted manuscript has been authored by a contractor of the U.S. Government under contract No. DE-AC05-84OR21400. Accordingly, the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U.S. Government purposes."

Prepared by
SOLID STATE DIVISION
OAK RIDGE NATIONAL LABORATORY
Managed by
LOCKHEED MARTIN ENERGY SYSTEMS
under
Contract No. DE-AC05-84OR21400
with the
U.S. DEPARTMENT OF ENERGY
Oak Ridge, Tennessee

August 1995

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

Microanalysis at the atomic level

S J Pennycook, D E Jesson, M M McGibbon,* A J McGibbon,* P D Nellist, and N D Browning†

Solid State Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831-6030

*Department of Physics and Astronomy, University of Glasgow, Glasgow G12 8QQ, Scotland

†University of Illinois at Chicago, Chicago, Illinois 60607-7059

ABSTRACT: The optical arrangement of the high-resolution scanning transmission electron microscope (STEM) allows incoherent imaging conditions to be established simultaneously for both elastically and inelastically scattered electrons, with good detection efficiencies. For zone axis illumination and localized inelastic transitions, both images show a resolution governed by the incident probe intensity profile, with maximum intensity occurring when the probe is located over the atomic columns. The high intensity elastic signal may therefore be used as an atomic resolution reference image for the low intensity inelastic signal, allowing spectroscopy to be achieved from selected atomic columns or planes. The potential of this approach in a 300-kV STEM is discussed.

1. ATOMIC RESOLUTION SPECTROSCOPY

The ease with which simultaneous detection of elastically and inelastically scattered electrons may be achieved in the STEM was one of the motivations for the development of the instrument by Crewe and coworkers in the late 1960's and early 1970's (Crewe, Wall, and Langmore, 1970, Crewe, Langmore, and Isaacson 1975). The complementary nature of the information in each channel was well appreciated. Now that the incoherent imaging of zone axis crystals is well understood (Pennycook and Jesson, 1990, 1991, 1992, Jesson and Pennycook, 1993, 1995), relying in thick crystals on the channelling of a coherent probe along the atomic columns, it becomes clear that the same phenomenon will also allow electron energy loss spectra to be collected at atomic resolution, allowing the analysis of specific atomic columns selected from the image. The use of high efficiency CCD based parallel detectors to minimise beam damage (McMullan et. al. 1990) now opens up the possibility of studying impurity segregation effects at interfaces and dislocation cores at a new level of sensitivity.

The criteria for incoherent imaging with inelastically scattered electrons was examined by Ritchie and Howie (1988) for an arbitrary probe wave function under kinematic scattering conditions (ie the probe wave function was unaffected by dynamical diffraction). They found that provided all the inelastic scattering was collected by the spectrometer the image intensity $I'(\mathbf{R})$ was given by the convolution of the probe intensity profile $P^2(\mathbf{R})$ with an object function $O'(\mathbf{R})$,

$$I'(\mathbf{R}_0) = \int P^2(\mathbf{R} - \mathbf{R}_0) O'(\mathbf{R}) d\mathbf{R} \quad (1)$$

which takes the form of an optical equation for incoherent imaging with an object function

$$O'(\mathbf{R}) = \left(\frac{e^2}{\pi \hbar v} \right)^2 \left| \int \frac{\rho_{no}}{q^2}(\mathbf{q}) e^{-i\mathbf{K} \cdot \mathbf{R}} d\mathbf{K} \right|^2 \quad (2)$$

where ρ_{no} are the atomic transition matrix elements from the initial state $|0\rangle$ to the final state $|n\rangle$. Calculations of the width of this object function have been made using a hydrogenic approximation involving excitation of a K-shell electron to the continuum with ejection of a secondary electron (Maslen and Rossouw, 1983, 1984, Rossouw and Maslen, 1984, Allen and Rossouw, 1990, Allen, 1993). Averaging over all directions of ejection of the unobserved secondary electron gives the required object function. Figure 1 shows the full width half maxima of object functions calculated in this way for a number of elements, and it is clear that even for the lightest elements this is below 1 Å. This results from the strong Z dependence of the hydrogenic model, and differs significantly from estimates based on the angular widths of the scattering distributions which are shown as the dashed lines in the figure (Pennycook, 1982, 1988). Furthermore, there is little dependence on beam energy. No equivalent model exists for L shell excitations, although recently Holbrook and Bird (1995) have calculated object functions for bound-to-bound transitions in a hydrogenic model, and find widths for L-shell excitations very comparable to those for K-shell excitation at comparable energy loss. Thus, atomic-resolution spectroscopy is feasible for all K and L lines of interest, limited primarily by the STEM probe size.

Fig. 1. Full width half maxima of object functions for K-shell excitation of various elements calculated with a hydrogenic model for a 50 eV ejected secondary assuming all scattered electrons are collected. Circles are for 100 kV incident electrons, crosses for 300 kV. Dashed lines show impact parameters estimated from the angular widths of scattering distributions.

With high energy losses the angular distribution becomes quite broad in reciprocal space and it is no longer possible to collect all the scattered electrons. Provided the collection aperture remains significantly broader than the probe forming aperture the situation can be handled by expressing the object function in reciprocal space (Whelan, 1965),

$$\tilde{O}'(\mathbf{K}) = \left(\frac{2e^2}{\hbar v} \right)^2 \int \frac{\rho_{\text{no}}(\mathbf{q}')}{q'^2} \frac{\rho_{\text{no}}^*(\mathbf{q}' + \mathbf{K})}{|\mathbf{q}' + \mathbf{K}|^2} d\mathbf{K}' \quad (3)$$

where

$$O'(\mathbf{R}) = \frac{1}{(2\pi)^2} \int \tilde{O}'(\mathbf{K}) e^{i\mathbf{K} \cdot \mathbf{R}} d\mathbf{K} \quad (4)$$

and then restricting the range of integration in Eq. 4 to the collector aperture. The effect is seen in Fig. 2 for the Si K excitation by a 100 kV electron beam (energy loss of 1840 eV). The intrinsic width if all scattered electrons could be collected is 0.24 Å, broadening to 0.93 Å for a 30 mrad collector and 1.34 Å for a 20 mrad collector, still both less than the 2.2 Å probe size (Pennycook, Jesson and Browning, 1995).

Fig. 2. Reduction and broadening of the Si-K shell object function due to the use of a finite collection aperture.

These results indicate that atomic resolution spectroscopy is perfectly feasible for the majority of core losses using a high resolution STEM, as experimentally demonstrated using an atomically abrupt CoSi₂/Si(100) interface as a resolution test specimen (Browning, Pennycook and Chisholm 1993). The integrated Co-L excitation dropped from 86% to 7% of its bulk value in moving from the last plane of the silicide to the first plane of Si, a distance of only 2.7 Å.

2. AN ATOMIC-RESOLUTION REFERENCE IMAGE

It is well known that if it were possible to collect all elastically scattered electrons an incoherent image would result with an object function $O(\mathbf{R})$ given by

$$O(\mathbf{R}) = \sigma^2 V^2(\mathbf{R}), \quad (5)$$

where $\sigma = \chi/2E$ is the interaction constant and $V(\mathbf{R})$ is the projected potential (Pennycook, Jesson, and Browning 1995). However, because a significant fraction of the total scattering occurs over the same angular range as the incident probe it is not practically possible to collect all the scattering. One can however detect a representative fraction of the total scattering with a high angle annular detector (Jesson and Pennycook, 1993), in which case the object function becomes the much sharper function

$$O(\mathbf{R}) = \sigma^2 |V(\mathbf{R}) * d(\mathbf{R})|^2 \quad (6)$$

where $d(\mathbf{R})$ is the Fourier transform of the annular detector function $D(\mathbf{K})$, which is unity over the detector and zero elsewhere. For incoherent imaging to be a good approximation, $d(\mathbf{R})$ must be significantly narrower than $P(\mathbf{R})$. Scattering from the sharp part of the projected potential also enhances the Z dependence of the image. We refer to this situation as transverse incoherence, since the strength of the object function increases as the square of the projected potential. Depending on detector angle, this coherence along the beam direction may be broken by thermal vibrations (Jesson and Pennycook, 1995). To study this effect it is necessary to use a phonon model of diffuse scattering; in an Einstein model the diffuse scattering is by definition generated incoherently. A model due to Warren (1990) shows clearly how near neighbours in a column are correlated in position and therefore scatter coherently, whereas atoms far apart scatter incoherently. The coherence length depends on detector angle as shown in Fig. 3 for a column of Rh atoms 2.7 Å apart illuminated by 300 kV electrons. With low detection angles the scattering is almost entirely coherent, becoming almost entirely incoherent at high detector angles. Intermediate angles exhibit an initial coherent dependence on thickness changing to an incoherent dependence as the column becomes significantly longer than the correlation length.

3. PROBE CHANNELLING

The kinematic models of incoherent imaging described above are only useful in real materials because of the remarkable channelling effect of a coherent STEM probe in a zone axis crystal. Because only tightly bound Bloch states survive the angular integration over the probe, we are effectively imaging only with tightly bound states (Pennycook and Jesson 1990, 1991, 1992). This removes the thickness dependence due to beating with less localized states, and also the non-local effects from images of interfaces, making possible the intuitive interpretation of incoherent images from thick crystals. When the s states are scattered completely to the detector the column intensity saturates. In thick crystals relative column contrast will therefore be less than the Z^2 dependence of the atomic cross section, although experimentally the heavier columns do always image brighter. Eventually the heavier material must image darker due to multiple scattering to angles too high to be detected; however, at such thicknesses no atomic resolution image remains. If inelastic transitions were as localised as the high angle elastic scattering, the probe channelling effect would be identical, delaying the onset of beam broadening, and allowing the spectroscopy of single planes or columns either side of an interface. In fact, the object function is typically substantially broader and we might anticipate an increasing importance of less localised states away from the atom sites. This point remains to be investigated.

a

b

c

Fig. 3. Thickness dependence of detected intensity from a column of Rh atoms spaced 2.7 Å apart along the beam direction calculated using a phonon model of diffuse scattering for inner detector angles of (a) 15, (b) 30, and (c) 45 mrad. Solid line shows the coherent component, dashed and dotted lines show the diffuse component calculated in the Einstein and Warren approximations respectively.

If the structure does not project the image contrast will be more complicated; images of defects or interface steps in the incoherent mode remain to be calculated. For the time being much is possible by choosing those regions that do project well giving clear images of interfacial structure.

4. DIRECT DETERMINATION OF INTERFACIAL STRUCTURE AND BONDING

The incoherent nature of the Z-contrast image allows its direct inversion to the projected structure, effectively bypassing the phase problem of conventional high resolution imaging (Pennycook et. al. 1992). A maximum entropy method due to Gull and Skilling (1984) has proved most useful in this regard, allowing column coordinates to be determined directly from experimental data to an accuracy of approximately 0.2 Å. Intensities are more susceptible to the effects of image shot noise than column positions, and column identities are best assigned by extrapolating from a perfect crystal into the region of interest (McGibbon and Pennycook 1995). This has allowed dislocation core structures to be determined in a CdTe film on GaAs using the 1.3 Å resolution of the VG Microscopes HB603 to image the sublattice directly (McGibbon, Pennycook, and Angelo 1995). In the case of SrTiO₃, using the HB501UX which is equipped with a parallel EELS system, oxygen coordination at grain boundaries was determined by the fine structure in core loss spectra obtained from the boundary plane. Structure models could be determined directly by this strategy, as shown in Fig. 4 for a 25° symmetric [001] tilt grain boundary (McGibbon et. al 1994). Features not considered in prior structure models include the hatched columns, definitively indicated by the incoherent image, and both apparently Sr from their positions in each crystal, but clearly too close to be fully occupied. These columns are presumed half occupied, alternating between the two halves of the bicrystal, which is an appealing solution to the problem of like-ion repulsion in ionic grain boundaries. The observation of the triangular structural units, primitive dislocation cores, is also somewhat unexpected and introduces a microscopic asymmetry into the boundary structure (Browning et. al., 1995). Furthermore, two variants were found, with and without a central Ti-O column. Such models invite speculation on likely segregation sites and represent ideal starting points for theoretical studies.

Fig. 4. (a) Maximum entropy image of a 25° symmetric [001] tilt grain boundary in a SrTiO₃ bicrystal. (b) Deduced atomic structure. Note the microscopic asymmetry of the boundary structure.

5. SPECTROSCOPY IN THE 300 KV STEM

Although we do not at present have a spectrometer on the 300-kV STEM, there is much to be said for one. The widths of the inelastic object functions are practically unchanged on increasing the accelerating voltage to 300 kV, as shown in Fig 1, but the intrinsic probe size is substantially smaller, 1.3 Å for the HB603 as compared with 2.2 Å for our 100-kV machine. The effective resolution is therefore significantly enhanced. An indication of the potential for simultaneous imaging and spectroscopy with this machine is seen from Fig 5, showing a Ni precipitate at a ZrO_2/NiO interface in a directionally solidified eutectic. Although oxygen does not contribute to the dark field image, one can immediately infer that the terminating plane of the ZrO_2 is oxygen from the distance between the last Zr plane and the first Ni plane in the precipitate. With an EELS capability it would be possible to quantify the charge transfer at these two different types of interface.

Fig. 5. Bright field (left) and dark field (right) images of a Ni precipitate at a ZrO_2/NiO interface, obtained simultaneously on a VG Microscopes HB603. Beam direction is along $[110] \text{NiO}/[001] \text{ZrO}_2$.

6. ACKNOWLEDGMENTS

The authors are grateful to V. P. David, V. Ravikumar and E. C. Dickey for collaborations, and J. T. Luck and T. C. Estes for technical assistance. This research was sponsored by the Division of Materials Sciences, U.S. Department of Energy, under contract No. DE-AC05-84OR21400 with Lockheed Martin Energy Systems.

REFERENCES

- Allen, L J 1993 Ultramicroscopy 48 97
- Allen, L J and Rossouw, C J 1990 Phys Rev B 42 11644
- Browning, N D, Chisholm, M F and Pennycook, S J 1993 Nature 366 143
- Browning, N D, Pennycook, S J, Chisholm, M F, McGibbon, M M and McGibbon, A J 1995 Interface Science 2 397
- Crewe, A V, Langmore, J P and Isaacson, M S 1975 Physical Aspects of Electron Microscopy and Microbeam Analysis, eds B M Siegel and D R Beaman (New York: Wiley and Sons) pp. 47-62

- Crewe, A V, Wall, J and Langmore, J 1970 Science **168** 1338
Gull, S F and Skilling, J 1984 EEE Proc. **131F** 646.
Holbrook, O F and Bird D M 1995 (in press) Proc. MSA 95
Jesson, D E and Pennycook, S J 1993 Proc. R. Soc. Lond. A **441** 261
Jesson, D E and Pennycook, S J 1995 Proc. R. Soc. Lond. A **449** 273
Maslen, V W and Rossouw, C J 1983 Phil Mag A **47** 119
Maslen, V W and Rossouw, C J 1984 Phil Mag A **49** 735
McGibbon, A J, Pennycook, S J and Angelo, J E 1995 Science **269** 519
McGibbon, A J and Pennycook, S J 1995 (in press) J. Microscopy
McGibbon, M M, Browning, N D, Chisholm, M F, McGibbon A J, Pennycook, S J, Ravikumar, V and Dravid, V P 1995 Science **266** 102
McMullan, D, Rodenburg, J M, Murooka, Y and McGibbon, A J 1990 Inst. of Phys. Conf. Ser. **98** 55.
Pennycook, S J 1982 Contemporary Physics **23** 371
Pennycook, S J 1988 Ultramicroscopy **26** 239
Pennycook, S J and Jesson, D E 1990 Phys. Rev. Lett. **64** 938
Pennycook, S J and Jesson, D E 1991 Ultramicroscopy **37** 14.
Pennycook, S J and Jesson, D E 1992 Acta Metall. Mater. **40** S149
Pennycook, S J, Jesson, D E, Chisholm, M F, Ferridge, A G and Seddon M J 1992 Scan. Microsc. Suppl **6** 233
Pennycook, S J, Jesson, D E and Browning, N D 1995 Nucl. Instr. and Meth. B **96** 575
Ritchie, R H and Howie, A 1988 Phil Mag A **58** 753
Rossouw, C J and Maslen, V W 1984 Phil Mag A **49** 749
Warren, B E 1990 X-Ray Diffraction (Dover, New York)
Whelan, M J 1965 J Appl Phys **36** 2099