FEB 26 1998

ENGINEERING DATA TRANSMITTAL

Page 1 of 1

1. EDT

620800

2. To: (Receiving Organization) Distribution		3. From: (Originating Organization) SNF Characterization Project		4. Related EDT No.:	
5. Proj./Prog./Dept./Div.: Spent Nuclear Fuel Project		6. Design Authority/ Design Agent/Cog. Engr.: N/A T. A. Flament		7. Purchase Order No.: N/A	
8. Originator Remarks: Drying studies, performed in France, for uranium hydrate.				9. Equip./Component No.: N/A	
				10. System/Bldg./Facility: N/A	
11. Receiver Remarks: 11A. Design Baseline Document? ☐ Yes ☒ No				12. Major Assm. Dwg. No.: N/A	
				13. Permit/Permit Application No.: N/A	
				14. Required Response Date: N/A	

15. DATA TRANSMITTED					(F)	(G)	(H)	(I)
(A) Item No.	(B) Document/Drawing No.	(C) Sheet No.	(D) Rev. No.	(E) Title or Description of Data Transmitted	Approval Designator	Reason for Transmittal	Originator Disposition	Receiver Disposition
1	HNF-2262		0	THERMAL DECOMPOSITION OF $UO_3 \cdot 2H_2O$	N/A	1,2		

16. KEY											
Approval Designator (F)		Reason for Transmittal (G)				Disposition (H) & (I)					
E, S, Q, D or N/A (see WHC-CM-3-5; Sec.12.7)		1. Approval 2. Release 3. Information		4. Review 5. Post-Review 6. Dist. (Receipt Acknow. Required)		1. Approved 2. Approved w/comment 3. Disapproved w/comment		4. Reviewed no/comment 5. Reviewed w/comment 6. Receipt acknowledged			
17. SIGNATURE/DISTRIBUTION (See Approval Designator for required signatures)											
(G) Reason	(H) Disp.	(J) Name	(K) Signature	(L) Date	(M) MSIN	(G) Reason	(H) Disp.	(J) Name	(K) Signature	(L) Date	(M) MSIN
		Design Authority									
		Design Agent									
1	1	Cog. Eng. T.A. Flament		R3-86							
1	1	Cog. Mgr. LA Lawrence for QA		H0-40							
		RP Umberg (See BTK. 20)									
		Safety									
		Env.									
18. B.J. Makenas Signature of EDT Originator		19. R.P. Umberg Design Authority/Cognizant Manager		20. R.P. Umberg Design Authority/Cognizant Manager		21. DOE APPROVAL (if required) Ctrl. No. ☐ Approved ☐ Approved w/comments ☐ Disapproved w/comments					

THERMAL DECOMPOSITION OF $UO_3 \cdot 2H_2O$

T. A. Flament

Numatec Hanford, Richland, WA 99352

U.S. Department of Energy Contract DE-AC06-96RL13200

EDT/ECN: 620800

UC: 2070

Org Code: 2T720

Charge Code: LB074

B&R Code: EW7040000

Total Pages: 74, 75

Key Words: K Basin, Uranium Hydrate, Thermo-Gravimetric Analysis

Abstract: The first part of the report summarizes the literature data regarding the uranium trioxide water system. In the second part, the experimental aspects are presented. An experimental program has been set up to determine the steps and species involved in decomposition of uranium oxide di-hydrate. Particular attention has been paid to determine both loss of free water (moisture in the fuel) and loss of chemically bound water (decomposition of hydrates). The influence of water pressure on decomposition has been taken into account.

TRADEMARK DISCLAIMER. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors.

Printed in the United States of America. To obtain copies of this document, contact: Document Control Services, P.O. Box 950, Mailstop H6-08, Richland WA 99352, Phone (509) 372-2420; Fax (509) 376-4989.

Janis Carolal 2-26-98
Release Approval Date

Release Stamp

Approved for Public Release

RESEAU EURISYS

78182 ST QUENTIN YVELINES CEDEX

FRANCE

Tél. + 33 1 39 48 50 00 - Télex 698316F

Fax : + 33 1 39 48 60 61

Type Doc.	Activité	Cat MT	N° d'ordre	Révision
NT	10510	00	0004	Rév. A

Unité	Emetteur	CMT	Situation
000	P25	00	0.000

PB/IL

TECHNICAL NOTE

THERMAL DECOMPOSITION OF $\text{UO}_3 \cdot 2\text{H}_2\text{O}$

Rev.	Written	Checked	Approved
A	P. BILARDELLO The 01-22-98	F. DRAIN The 01-22-98	F. DRAIN The 01-22-98

CHRONOLOGY OF REVISIONS**Rev.****Date, Review number, Signatories and identification of modified paragraphs**

A Approved on : 01. 22. 98

Control number : 97352000664

Written by : P. BILARDELLO

Checked by : F. DRAIN

Approved by : F. DRAIN

SUMMARY

1.	BACKGROUND AND PURPOSE.....	4
2.	URANIUM TRIOXIDE - WATER SYSTEM	5
2-1	URANIUM TRIOXIDE HYDRATES	5
2-2	THERMAL DECOMPOSITION OF DI-HYDRATE $UO_3 \cdot 2H_2O$	5
3.	EXPERIMENTAL.....	8
3.1.	SCOPE AND PROGRAM	8
3.2.	FIRST PHASE - SYNTHESIS OF MATERIALS	10
3.3.	SECOND PHASE : REACTION PATH.....	11
3-4	THIRD PHASE : KINETICS DATA	14
3-4	INTERPRETATION	16
4	KINETIC MODEL.....	18
4-1	MODEL DESCRIPTION	18
4-2	IDENTIFICATION METHOD	19
4-3	COMPUTER MEANS	20
4-4	RESULTS	20
5	CONCLUSION	21

BIBLIOGRAPHY.....	22
APPENDIX 1 EXPERIMENTAL DEVICE.....	24
APPENDIX 2 SECOND PHASE : DTG/ATD CURVES.....	27
APPENDIX 3 THIRD PHASE : TGD/TDA CURVES.....	35
APPENDIX 4 WATER PRESSURE.....	42
APPENDIX 5 WATER FREE.....	44
APPENDIX 6 KINETIC MODEL.....	48
APPENDIX 7 COMPARISON CURVES : RUNS USED IN IDENTIFICATION.....	51
APPENDIX 8 COMPARISON CURVES : RUNS CARRIED OUT WITH MOISTURE ATMOSPHERE.....	56
APPENDIX 9 WEIGHT SPECIES VARIATION.....	60
APPENDIX 10 X-RAY DIFFRACTION PATTERN RUN ES08 AND ES12 (AFTER 1H30MN OF HEATING TIME).....	64
APPENDIX 11 PREDICTED MAAS LOSS IN HEATING CONDITIONS OF KE CANISTER SLUDGE 96-08 (RUN 46 OF [10]).....	67
APPENDIX 12 PARTICULE-SIZE DISTRIBUTION OF THE TWO SAMPLES.....	69

1. BACKGROUND AND PURPOSE

This study is performed in the frame of the Spent Nuclear Fuel (S.N.F) project. The scope of the project is to remove fuel and sludge from basins and to pack it to ensure a storage complying with environmental constraints. The residence time in basins have induced some evolution of spent nuclear fuel. The uranium transformation into UO_3 hydrates and the fuel moisture require a drying process of spent nuclear fuels.

The literature provides very little information on decomposition rates of uranium oxides hydrates. These information are necessary to support the modelling of the drying process. The scope of this study is to determine $\text{UO}_3 \cdot 2\text{H}_2\text{O}$ decomposition rates as a function of temperature up to 400°C and water pressure in the range from 0 to 40 kPa.

The first part of the report summarises the literature data regarding the uranium trioxide water system

In the second part experimental aspect is presented. An experimental program has been set up to determine the steps and species involved in decomposition of uranium oxide di-hydrate. A particular attention has been paid to determine both loss of free water (moisture of the fuel) and loss of chemical bound water (decomposition of hydrates). The influence of water pressure on decomposition has been taken into account.

The experimental means are thermogravimetric analyses (T.G.A) coupled with differential thermal analysis (D.T.A.), X-ray diffraction, granulometric, and chemical analysis.

The third part of this report deals with the model to predict thermal decomposition of uranium oxide hydrate. The method used to built in the kinetic model, with an appropriate exploitation of experimental data, is explained.

Arguments about validity and limit of this model are developed in conclusion of this report.

2. URANIUM TRIOXIDE - WATER SYSTEM

2-1 URANIUM TRIOXIDE HYDRATES

Different crystalline phases and chemical compositions of uranium trioxide hydrates are listed in table 1.

All the authors agree on the presence of hydrates $\text{UO}_3 \cdot 2\text{H}_2\text{O}$; $\text{UO}_3 \cdot \text{H}_2\text{O}$; $\text{UO}_3 \cdot 0.5\text{H}_2\text{O}$. Discussion remains about the existence of hydrates $\text{UO}_3 \cdot x\text{H}_2\text{O}$ with $0.7 < x < 0.9$. These hydrates are usually named dehydrated schoepite (DS).

The effect of heat treatment on a pure monohydrate involves an irreversible distortion of $\text{UO}_3 \cdot \text{H}_2\text{O}$ crystalline lattice. [4] which induces a modification of the hydration degree. This distortion is identified with thermal gravimetric analysis coupling with X-ray diffraction. The X-ray patterns of the different dehydrated schoepite $\text{UO}_3 \cdot x\text{H}_2\text{O}$ are very similar. The peaks position are almost the same but the relative intensities are different (table 2).

2-2 THERMAL DECOMPOSITION OF DI-HYDRATE $\text{UO}_3 \cdot 2\text{H}_2\text{O}$

Dawson [5] and Danroc [3] have proposed the same thermal decomposition path although the experimental conditions were different :

The Danroc [3] conditions are ambient temperature during five hours followed by a temperature increase rate of $5^\circ\text{C}/\text{mn}$. The pressure is 10 torr. The Dawson [5] conditions is a temperature increase rate of $2^\circ\text{C}/\text{mn}$, and atmospheric pressure.

The purpose of Danroc works is to study UO_2 ageing in moisture atmosphere. The samples composition are mixtures of UO_2 and $\text{UO}_3 \cdot 2\text{H}_2\text{O}$.

In the case of Dawson [5], identification of uranium trioxide hydrates have been studied. The samples are constituted by pure $\text{UO}_3 \cdot 2\text{H}_2\text{O}$.

The $\text{UO}_3 \cdot \text{H}_2\text{O}$ are clearly identified by X-ray diffraction. The X-ray analysis don't permit to conclude between $\text{UO}_3 \cdot 0.8\text{H}_2\text{O}$ and β crystalline form of $\text{UO}_3 \cdot \text{H}_2\text{O}$. In the two works $\text{UO}_3 \cdot 0.8\text{H}_2\text{O}$ has been deduced from mass loss analysis in thermal decomposition process.

FORMULA	Molar weight g/mol	Weight percent				Loss mass percent - Base UO ₃ , 2(H ₂ O)
		U	O	H	H ₂ O	
UO ₂	270	88.15	11.85	-	-	16.15
UO ₃	286	83.22	16.78	-	-	11.18
U ₃ O ₈	842	84.80	15.20	-	-	12.84
UO ₃ , 2(H ₂ O)	322	73.91	24.84	1.24	11.18	-
UO ₃ , (H ₂ O)	304	78.29	21.05	0.66	5.92	5.59
UO ₃ , 0.8(H ₂ O)	300.4	79.23	20.24	0.53	4.79	6.71
UO ₃ , 0.5(H ₂ O)	295	80.68	18.98	0.34	3.05	8.39

Crystallography	Colour	Crystalline type
UO ₃	dark orange clear yellow	amorphous α
UO ₃ , 2(H ₂ O)	yellow green-yellow	α β
UO ₃ , (H ₂ O)	orange-yellow yellow	α β γ δ

Decomposition enthalpies and pressure equilibrium	ΔH kJ/mol	ΔH J/g	P (25°C) kPa	P (100°C) kPa	REF
UO ₃ , 2H ₂ O $\rightarrow$ UO ₃ , H ₂ O + H ₂ O	51.4	159.6	1.4	92.20575	[1]
UO ₃ , H ₂ O $\rightarrow$ UO ₃ , 0.8H ₂ O + 0.2H ₂ O	5.5	18.1			[3]
UO ₃ , 0.8H ₂ O $\rightarrow$ UO ₃ (am) + 0.8H ₂	77.6	258.3			[1]
UO ₃ , 2H ₂ O $\rightarrow$ UO ₃ + 2H ₂ O	120.1	373.0			[3]
UO ₃ , 2H ₂ O $\rightarrow$ UO ₃ (am) + 2H ₂ O	134.5	417.7			[1]
UO ₃ , H ₂ O $\rightarrow$ UO ₃ + H ₂ O	69.0	227.0			[3]
UO ₃ , H ₂ O $\rightarrow$ UO ₃ (am) + H ₂ O	83.1	273.4			[1]

Table 1 - Characteristics of hydrates

Peak position A	x value of $\text{UO}_3 \cdot x(\text{H}_2\text{O})$					
	2 (β)	1	0.9 (α)	0.84	0.8	0.5
7.35 6.89	100					20
5.09 5.1		100	80	100	80	
4.76 4.21						30 100
3.59 3.45 3.49 3.42-3.44 3.28 3.22	40	25 17	100	100 70	100 65	50 40
2.49-2.85 2.85 2.563 2.529 2.48 2.15 1.97-1.99	20 10	7 8	55 55 50	65 30 50	52 28	

Table 2 - X-ray diffraction pattern of $\text{UO}_3 \cdot x\text{H}_2\text{O}$ - relative intensities

3. EXPERIMENTAL

3.1. SCOPE AND PROGRAM

The experimental program has been divided into three phases.

The scope of the first phase is to synthesise the hydrate $\text{UO}_3 \cdot 2\text{H}_2\text{O}$.

This material has been synthesised in two ways from anhydrous UO_3 , by immersion into water and by sweeping wet air. In the first case, a mixture of UO_3 , $2\text{H}_2\text{O}$ and H_2O has been obtained in the second case pure $\text{UO}_3 \cdot 2\text{H}_2\text{O}$ has been obtained. These two ways of synthesis will allow during the second phase to determine during decomposition both loss of free water and loss of chemical bound water.

The final products are analysed using X-ray diffraction. The uranium composition of initial and final products are verified by chemical analysis. Granulometric analysis have been made on the two final products.

The second and third phase consists to study the thermal decomposition of these two products. A D.T.G./D.T.A. diagram is obtained for each run of the second and third phase. The diagram includes three curves for each run.

- The T.G. curve gives the mass loss percent, 100% corresponding to the initial mass sample.
- The D.T.G. curve gives the mass loss time derived.
- The D.T.A. curve gives the heat flow between sample and the heat spring.

A blank test is made for each experimental runs. It consists to apply the programmed temperature profile to a standard product (Al_2O_3) which is chemically stable in the used range of temperature. The initial mass is same as mass of sample and the recording of mass evolution allows to correct the base line of mass loss curve with respect of temperature evolution. All the curves submitted in this report take a specific blank test into account.

The accuracy of mass measurement is higher than 0.1 mg for a initial sample mass of 50 mg. This accuracy has been estimated for with a product (sodium oxalate) for which theoretical thermal decomposition is compared with measured mass loss.

The heat flow allows to evaluate the enthalpies of the different phenomena. Sensibility coefficient have been determinated in the temperature range of this study with known fusion enthalpies of standard metals. The accuracy is good for high temperature (10 % of the absolute value). For temperature less than 150 °C, sensibility coefficients are not known accurately. The enthalpies accuracy for temperature less than 150 °C is unknown, the enthalpies values is to take like an indication and not in absolute.

The main objective of the second phase is to obtain information on the various species involved during thermal decomposition and the influence of the water pressure .

The test have been performed using argon atmosphere with vapour pressure in the range of 0 to 40 kPa. The two different samples of $\text{UO}_3 \cdot 2\text{H}_2\text{O}$ have been used (with and without free water). The temperature range is from 20°C to 500°C. Two heating rate have been used (5°C/mn and 0,5 °C/mn).

The scope of the third experimental phase is to obtain enough experimental data to perform a suitable kinetic models. The experimental data have been obtained by heating samples at a constant temperature. The condition of temperature and water pressure, are adjusted according to the results of the precedent phase.

3.2. FIRST PHASE - SYNTHESIS OF MATERIALS

The UO_3 powder are synthesised in two steps :

- oxidation of dioxide uranium (UO_2) by hydrogen peroxide (H_2O_2) to yield uranium peroxide (UO_4)
- drying and calcination of UO_4 .

The UO_3 powder is grinded and characterised by x-ray diffraction. The amount of uranium is determined by chemical analysis.

The di-hydrate $\text{UO}_3 \cdot 2\text{H}_2\text{O}$ is then prepared either by sweeping wet air or by immersion in water. In the two cases, the preparation time is 148 hours. In the first case after 24h, the X-ray diffraction indicates that the sample is pure di-hydrate. The two samples of di-hydrates $\text{UO}_3 \cdot 2\text{H}_2\text{O}$ synthesised have the same X-ray diffraction and the same yellow colour at the end of preparation.

The table 3 summarises the reagents characteristics. The difference between measured and theoretical uranium percentage may result of the synthesis process of UO_3 . The UO_3 synthesised could not be completely anhydrous, a part could be already converted in hydrate. This hypothesis is confirmed by the negligible difference between theoretical and measured uranium percent in pure $\text{UO}_3 \cdot 2\text{H}_2\text{O}$.

The difference between theoretical and measured weight of U has been assimilated at free water. The calculated free water percent has been reported in table 3.

Appendix 12 presents the particle-size distribution of the two samples. The particle size distribution of the sample synthesised by immersion into water shows that 50 % of the population have a size less than 1 μm , and two size-distribution maximum have been identified, one at 1 μm and the other at 50 μm . The synthesis method could be induce the partial destruction of rubbles.

The particle-size distribution of di-hydrate synthesised by sweeping wet air shows that 50% of the population have a size less than 193,5 μm , the size-distribution is centered around 300 μm

	Weight Percent of U measured theoretical		Particule size 10e-6m	X-ray diffraction identification	Calculated water percent
UO_3 anhydrous	79.7	83.2	-	-	4.21
$\text{UO}_3 \cdot 2\text{H}_2\text{O}$ synthesised by sweeping wet air	73.6	73.9	193.5	$\text{UO}_3 \cdot 2\text{H}_2\text{O}$	0.41
$\text{UO}_3 \cdot 2\text{H}_2\text{O}$ synthesised by immersion into water	49.9	73.9	1	$\text{UO}_3 \cdot 2\text{H}_2\text{O}$	32.48

Table 3 - Phase 1 : Reagents characteristics

3.3. SECOND PHASE : REACTION PATH

Appendix 1 presents the experimental device, a slight modification have been made after the run ES03 to improve temperature control of inlet and outlet gases. This modification does not affect the results.

Table 4 indicates the experimental conditions of the seven experiments.

Table 5 summarises the results of mass loss and endothermic peaks.

Appendix 2 gathers the D.T.G/D T.A. curves of the first phase.

For all runs, the mass loss curve presents two plateau: the first between 150°C and 350°C, the second after 400°C. Two endothermic peaks (D.T.A. curves) can be associated with the two plateau : the first between 138 and 159°C and the second between 345°C and 364°C.

The curves of runs ES02 to ES06 presents a slight mass loss and an endothermic peak for temperature lower than 90 °C. This phenomena is linked to the experimental operating procedure used to fix a water pressure in wet atmosphere without condensation risk. The runs are started with dry gas; when saturation temperature is reached for a fixed water pressure the wet gas are send and the dry gas stopped.

The mass loss curve of run ES06 presents a third plateau after 475°C.

The run ES07 has been made with the sample n°1 which contains 32% of free water. The mass loss curve presents also two plateau, positions of which are the same but the mass loss is more important for the first plateau. Two supplementary endothermic peaks can be identified for temperature, lower than 160°C.

The X-ray diffraction patterns of the final products of all runs can be clearly identified UO_3 . For all runs except the run ES06, an amorphous phase can exist, the base line is not a continuous straight line. For the run ES06, the amorphous phase is not identified and the peak intensity of αUO_3 increase with regard to the other runs.

Three peaks of lower intensity could not be associated at a known product of the data bank data of JCPS [6].

ID. RUN	Water Pressure kPa	Temperature profiles	Initial weight mg	Sample origin
ES01	0	heated at constant rate of 5°C/mn to a temperature of about 400°C	72.6	2
ES02	5	heated at constant rate of 5°C/mn to a temperature of about 400°C	72.4	2
ES03	20	heated at constant rate of 5°C/mn to a temperature of about 400°C	70.32	2
ES04	20	heated at constant rate of 5°C/mn to a temperature of about 500°C	78.21	2
ES05	40	heated at constant rate of 5°C/mn to a temperature of about 500°C	66.76	2
ES06	20	heated at constant rate of 0.5°C/mn to a temperature of about 515°C	71.01	2
ES07	0	heated at constant rate of 5°C/mn to a temperature of about 500°C	117	1

Sample origin :

1 UO₃.2H₂O synthesised by immersion into water of anhydrous UO₃2 UO₃.2H₂O synthesised by sweeping wet air of anhydrous UO₃

Table 4 - Phase 2 : Experimental conditions

	ES01	ES02	ES03	ES04	ES05	ES06	ES07
Mass Loss (1)							
Temperature °C	250	250	250	250	250	250	250
Absolute mass loss Percent	7.04	6.62	7.55	7.34	6.71	8.04	35.6
Temperature °C	400	400	400	400	400	400	400
Relative mass loss percent	3.95	3.68	3.96	4.10	3.87	4.10	5.28
Absolute mass loss Percent	10.71	10.06	11.21	11.14	10.32	11.81	39
Temperature				500	500	515	515
Relative mass loss percent				4.38	4.16	4.81	5.56
Absolute mass loss Percent				11.4	10.59	12.46	39.18
Endothermic peaks (2)							
Peak temperature °C							92-116
Temperature range °C							28-155
Enthalpie J/g							470
Peak temperature °C	157.5	158	159	166	165	138	160
Temperature range °C	22-210	24-210	24-210	56-210	86-210	26-210	28-210
Enthalpie J/g	201	228	228	194	161	264	784
Peak temperature °C	350	352	355	363	364	337	345
Temperature range °C	250-405	250-405	250-405	290-415	280-420	290-370	280-400
Enthalpie J/g	140	138	135	138	150	169	65
Enthalpie J/g (total temperature range)	341	366	363	332	311	433	849
DX characterisation (end of runs)	amorph.	amorph.	amorph.	amorph.	amorph.	UO3 α	amorph.

(1) Relative mass loss is calculated in respect with the mass sample at 250 °C

(2) The peak temperature corresponds at the maximum of peak endothermic intensity

Table 5 - Phase 2 : Experimental results

3-4

THIRD PHASE : KINETICS DATA

Table 6 indicates the experimental conditions of the six experiments of the third phase. Three temperature have been chosen to confirm

- the reaction path
- the influence of free water at low temperatures
- the influence of water pressure at low temperatures

Appendix 3 gathers the DTG/ATD curves of this experimental phase

Table 7 summarises the results about mass loss, decomposition time and X-ray diffraction

The monohydrate are clearly identified by X-ray diffraction for runs ES08 to ES11. At the end of the run ES12 we are probably in presence of amorphous phase of UO_3 . This run has been made repeated, a X-ray diffraction analysis after 1h30mn of heating detected a presence of monohydrate $\text{UO}_3 \cdot \text{H}_2\text{O}$

The mass loss of the run ES13 is very light and the major product is the di-hydrate β -phase

ID. RUN	Water Pressure kPa	Temperature profiles	Initial weight mg	Sample origin
ES08	0	heated at constant rate of 5°C/mn to a temperature of about 100°C and plateau at this temperature within weight changes is neglected	68.48	2
ES09	0	heated at constant rate of 5°C/mn to a temperature of about 100°C and plateau at this temperature within weight changes is neglected	134.9	1
ES10	0	heated at constant rate of 5°C/mn to a temperature of about 75°C and plateau at this temperature within weight changes is neglected	69.04	2
ES11	0	heated at constant rate of 5°C/mn to a temperature of about 75°C and plateau at this temperature within weight changes is neglected	159.4	1
ES12	0	heated at constant rate of 5°C/mn to a temperature of about 250°C and plateau at this temperature within weight changes is neglected	96.94	2
ES13	20	heated at constant rate of 5°C/mn to a temperature of about 75°C and plateau at this temperature within weight changes is neglected	75.82	2

Sample origin

- 1 UO₃.2H₂O synthesised by immersion into water of anhydrous UO₃
- 2 UO₃.2H₂O synthesised by sweeping wet air of anhydrous UO₃

Table 6 - Phase 3 : Experimental conditions

	ES08	ES09	ES10	ES11	ES12	ES13
Mass Loss						
Time	2h30	2h00	7h00	7h00	1h00	3h00
Absolute mass loss Percent	6.96	34.27	6.06	27.22	7.46	0.79
Time	10h00	6h00	17h00	17h00	6h00	19h00
Absolute mass loss Percent	7.12	34.37	6.26	34.73	8.73	1.32
DX characterisation 1h30mn (end of runs)	UO ₃ .H ₂ O	UO ₃ .H ₂ O	UO ₃ .H ₂ O	UO ₃ .H ₂ O	UO ₃ .H ₂ O amorph. UO ₃	UO ₃ .2H ₂ O

Table 7 - Phase 3 : Experimental results

3-4 INTERPRETATION

Reaction path

The first plateau of the mass loss curves (ES01, ES02, ES03 ...) cannot correspond to the monohydrate $\text{UO}_2 \cdot \text{H}_2\text{O}$. The theoretical mass loss is 5,6% (table 1), and experimental plateaux correspond at a mass loss between 6.6% and 8% (table 5).

The mass loss between the first and the second plateau is included between 3.7% and 4.1% for run ES01 to ES06. This result is closer to theoretical mass loss of $\text{UO}_3 \cdot 0.8\text{H}_2\text{O}$ than to theoretical mass loss of others hydrates.

The total mass loss, the X-diffraction analysis and the total endothermic enthalpy of run ES01 to ES06 confirm that the final product is UO_3 anhydrous. The crystalline form is amorphous or α . The mass loss curve of the run ES06 and X-ray diffraction shows that a final step of anhydrous UO_3 decomposition occurs when the residence time is sufficient.

The X-diffraction analysis of the third experimental phase identified only the $\text{UO}_3 \cdot \text{H}_2\text{O}$ like intermediate hydrate in the decomposition process. In X-ray diffraction, patterns identified like $\text{UO}_3 \cdot \text{H}_2\text{O}$ is slightly different between ES08 and ES12 after a heating time of 1h30mn (Appendix 10). The relative intensities of peaks is different compared with standard $\text{UO}_3 \cdot \text{H}_2\text{O}$ X-ray diffraction pattern (table 2), and the main peaks are not in the same position.

The $\text{UO}_3 \cdot 0.8\text{H}_2\text{O}$ hydrate is not clearly identified with X-ray diffraction analysis but the mass loss curves show that another hydrate is involved in reaction path and the X-ray patterns of the various $\text{UO}_3 \cdot x\text{H}_2\text{O}$ hydrates ($0.7 < x < 0.9$) are very similar (paragraph 2-1). So, the reaction path proposed is the same that Dawson [5] and Danroc [3].

For the kinetic model the step 3a will not be taken into account.

Free water

Mass loss experimental curves of runs with the two samples (with and without free water) are presented in appendix 5. The comparison between a runs carried out with and without free water shows that the loss of free water is faster than the loss of chemically bound water of hydrates. The loss of free water does not seem to affect the kinetic of decomposition of hydrate

Water pressure

Appendix 4 present experimental mass loss curves of runs carried out with various atmosphere. It is not possible to conclude a consistent influence of water pressure. But the last run ES13, carried out with a water pressure of 20 kPa, shows a very small mass loss after 19h00 of heating time at 75 °C (1.3%) compared to ES10 carried out with dry atmosphere (6.26%).

Two phenomena are competing a hydrates chemical decomposition and a diffusion of water product by chemicals reactions between the sample surface (boundary layer) and the bulk atmosphere phase. The diffusion rate is proportional to water concentration gradient between boundary layer and bulk phase. The maximum pressure in the boundary layer is determined by the equilibrium water pressure of decomposition reaction. Figure 1 shows the variation of equilibrium pressure of di-hydrate decomposition in monohydrate with thermodynamic data of [5] (Table 1). The experimental point 75 °C and 20 kPa (ES13) is very close to the equilibrium pressure. So the concentration gradient is small. In the runs ES04, ES05, ES06 the gradient increase like water equilibrium pressure with heating time, for this runs the diffusivity phenomena can be neglected.

Figure 1 Water equilibrium pressure dihydrate first decomposition step

4 KINETIC MODEL

4-1 MODEL DESCRIPTION

The appendix 4 presents the kinetic model. The following hypothesis have been made.

- The model is based on only on chemical kinetic laws. The model suppose that the diffusion rates is sufficiently higher than kinetic rate to allow to neglect diffusion phenomena.
- The rate of reactions does not depend on products. So, the water pressure is neglected in the kinetic law.
- The kinetic constant follows the Arrhenius law.

The model is a system of differential algebraic equations. The amount of each species can be estimated with this dynamic model at each time.

4-2 IDENTIFICATION METHOD

The identification method consist to estimate the eight unknown variables which are pre-exponential factor and activation energy of each decomposition rate.

The steps of the method are the followings.

- Choice of experiment for identification. We choose runs which have been carried out with dry atmosphere, and with pure di-hydrate (ES01, ES08, ES10, ES12). The run ES06 have been used to identify the pre-exponential factor and activation energy of the last reaction of transformation of UO3 in U3O8.
- Acquisition of experimental data. For each runs we take into account the initial condition (mass of di-hydrate and temperature) . For each acquisition time, the temperature and the mass sample is used in identification. The acquisition frequency is about a few minutes.
- Numerical resolution. A modified Gauss-Newton method is used to minimise the experimental data-model RMS deviation with respect to unknown variables. The unknown variables are reconditioned to decrease numerical convergence problems. The modification of Gauss-Newton method consists to take into account the model dynamic characteristic. A Gear method is used to solve differential algebraic system.
- Experiment-model comparison. For each run used in identification, comparison curves are drawn to compare experimental data and model estimation of mass loss.
- Influence of water pressure. The run carried out with moisture atmosphere are also used to compare experimental and model estimated mass loss.

4-3 COMPUTER MEANS

The experimental data are ASCII files which are treated with EXCEL software [7]. The identification are carried out with Speedup software [8].

4-4 RESULTS

Table 8 shows the best fit Arrhenius parameters of model. Appendix 7 and 8 gathers comparison curves achieved with these parameters. Appendix 7 concerns runs used in parameters identification and appendix 8 runs carried out with moisture atmosphere. Appendix 9 shows the weight species variation versus time

The model can describe with very good agreement mass loss variation in thermal decomposition of pure di-hydrate in a dry atmosphere (appendix 7).

The weight species variation (appendix 9) predict that at the end of all experiment samples are constituted in majority of monohydrate (ES08 and ES10) or anhydrous UO₃ (ES12, ES01). These results are in agreement with X-ray diffraction measures (table 6). The inconsistency of the model prediction concerns the run ES12 where the models predicts that the hydrates UO₃.0.8H₂O is preponderant after 1h30mn of thermal decomposition and the X-ray diffraction measure identifies the monohydrate. The literature data shows that is difficult to distinguish the different dehydrated schoepite UO₃.xH₂O with X-ray diffraction analysis (table 2).

The variation of mass loss for runs carried out in a moisture atmosphere can also been described with this model exempt for run ES13 (75 °C, 20kPa). This results confirms that for runs ES02 to ES06, the heating conditions permits to neglect the diffusion phenomena.

	Pre-exponential factor s-1	Activation energy J/mol
UO ₃ .2H ₂ O ---> UO ₃ .H ₂ O + H ₂ O	258069	61886
UO ₃ .H ₂ O ---> UO ₃ .0.8H ₂ O + 0.2H ₂ O	1.17E+28	243456
UO ₃ .0.8H ₂ O ---> UO ₃ + 0.8H ₂ O	6906	77268
UO ₃ ---> (1/3) U ₃ O ₈ + (2/6) O ₂	1.34E-02	31236

Table 8 - Best-fit Arrhenius parameters

5 CONCLUSION

This study has allowed to acquire a better knowledge of hydrates trioxide uranium thermal decomposition.

The main results of experimental program are :

- The thermal decomposition of dihydrate ends to anhydrous UO_3 or U_3O_8 , if residence time and temperature are enough. The monohydrate is identified like one of the intermediate product in the decomposition chemical path. The analysis of thermogravimetric measures shows that other chemical species seems to be involved in the decomposition chemical path
- The restrictive step in the drying process is the chemical decomposition of hydrate. The loss of free water is faster than the kinetic of decomposition
- The water pressure of the bulk atmosphere phase is a key parameter in the low temperature range. The diffusion seems to be the restrictive phenomena compared to the chemical decomposition

A kinetic model has been optimised in respect with experimental mass loss measures. This model allows to obtain decomposition rates of different species and propose a suitable reaction path..

This model will be used to choose and optimise the drying process of spent nuclear fuel. The appendix 11 shows the mass loss estimated by the model for heating conditions used in K-East canister sludge samples [10]. The value of mass loss estimated does not correspond to experimental results, but the model predict with good agreement the time when the decomposition ended. These facts confirm that the chemical decomposition is the restrictive phenomena in drying process and they shows the suitable values of decomposition rates in the range of 20°C to 600°C.

BIBLIOGRAPHY

- [1] HOEKSTRA H.R., SIEGEL S.
 "The uranium trioxide - water system"
 J. Inorg and Chem, Vol.35, pp761-779 (1973)

- [2] BERG L. and Col.
 U₃O₈ oxides and UO₃ hydroxide hydrates and peroxides
 Gmelin handbook of inorganic chemistry
 Supplementary volume part C2
 Main serie, 8th Edition (1978)

- [3] DANROC J.
 "Evolution superficielle it aptitude an compactage des poudres de dioxyde d'uranium"
 PhD Institut national polytechnique de Grenoble (1982)

- [4] KUZNETSOV L.M. and TSVIGUNOV A.N.
 "Effect of heat treatment on physical parametry of uranium trioxide hydrates (UO₃ (1-x) H₂O)"
 Radiokhimiya, vol.25, n°5, pp 652-656 (1983)

- [5] DAWSON J.K., WAIT E., ALCOCK K., CHILTON D.R.
 "Some aspects of the system uranium trioxyde - water"
 J. of chemical Society pp 3531-3540 (1956)

- [6] P.A.G. O'HARE P.A.G., BRETT M. LEWIS, SON N. NGUYEN
 "Thermochemistry of uranium compounds
 XVII: Standard molar enthalpy of formation at 298.15 K. of dehydrated schoepite UO₃ 0.9H₂O. Thermodynamics of (schoepite + dehydrated schoepite+water)
 J. Chem. Thermodynamic, 20, 1287-1296 (1988)

- [7] TAYLOR P., WOOD D.D., DUCLOS A.M., OWEN D.G.
 "Formation of uranium trioxide hydrates on UO₂ fuel in air-steam mixtures near 200°C"
 Journal of Nuclear Materials 168, 70-75 (1989)

- [8] EXCEL software
Microsoft Exel version 4.0 (1992)

- [9] SPEEDUP software
version 5.5
Aspen Technology Inc. (1997)

- [10] ABREFAH J., BUCHANAN H.C., MARSCHMAN S.C., MAKENAS B.J.
"Highlight Report: Third report on drying behavior of K-East Canister Sludge"
SNFCT 97:044:R00 (1997)

APPENDIX I**EXPERIMENTAL DEVICE**

The experimental operating is applied for all runs of second phase and third phase and for accuracy test

Experimental operating

Place the sample into a clean tared instrument holder (80 +/- 30 mg)

Sweeping with a maximum gas flow rate for 15 mn

Maintain a constant flow rate in the range from 40 to 50 ml/mn

When the mass variation can be neglected (+/- 0.05 mg) the initial sample mass is recorded and the heating profile can be started. The mass loss and the heat flow between furnace and sample are recorded .

Started runs with dry gas, when saturation temperature is reached for a fixed water pressure the wet gas are send and the dry gas stopped.

When the heating profile is finished, the system is cooled at room temperature

A standard product (AL₂O₃) is put in place of the sample and the all precedent steps are repeated. This blank test allows to correct the base line of mass loss curve with respect of temperature evolution.

Accuracy test

The different steps are also applied at sodium oxalate for which theoretical thermal decomposition is well now with a heating rate of 5°C/mn. The accuracy of mass measurement is higher than 0.1 mg.

Sensibility coefficients for heat flow measurement have been determinate in the temperature range from 150 to 350 °C. The coefficients have been determined with known fusion enthalpies of standard metals. In the experimental temperature range the accuracy is higher than 10 % of the absolute value.

APPENDIX 2**SECOND PHASE : DTG/ATD CURVES**

Fig.: Echant: UO3.2H2O, 20/50C, 5C/mn, 5mn, 50/500C, 5C/mn, 20KPaH2O
 29-09-97 P: 20/50, 5C/mn, pailier 5mn, 50/500, 5C/mn

Masse: 78.21 mg Atm: Ar+H2O
 Ctn: A1203

E 304

APPENDIX 3**THIRD PHASE : TGD/TDA CURVES**

BETARAM
T60TA92

Fig.: Echant: U03.2H2O (2), 20/100C, 5C/mn, palier 105C, 10h, Ar sec
14-10-97 P: 20/100C, 5C/mn, palier 100C sur 10h E508

Masse: 68.48 mg Atm: Ar
Ctn: A1203

SCN
RESEAU EURIS

Type Doc. : Analyse
NT 10510 00 0004 Rév. A
Ch. NT
N° Fichier : Révision

Page: 37/74

HNF-2262 Rev. 0

APPENDIX 4**WATER PRESSURE**

APPENDIX 5

WATER FREE

Ramp of 5 C/min

Type Doc.	Activité	Cat MT	N° d'ordre	Révision
NT	10510	00	0004	Rév. A

Temperature dwell at 75 C

Page : 47 / 74

Type Doc	Activité	Cat NT	N° Usine	Révision
NT	10510	00	0004	Rev. A

Temperature dwell at 105 C

APPENDIX 6**KINETIC MODEL**

Thermal decomposition of $\text{UO}_3 \cdot 2\text{H}_2\text{O}$

reactions

1. $\text{UO}_3 \cdot 2\text{H}_2\text{O} \rightarrow \text{UO}_3 \cdot \text{H}_2\text{O} + \text{H}_2\text{O}$
2. $\rightarrow \text{UO}_3 \cdot 0.8\text{H}_2\text{O} + 0.2 \text{H}_2\text{O}$
3. $\rightarrow \text{UO}_3 + 0.8 \text{H}_2\text{O}$
4. $\rightarrow 1/3 \text{U}_3\text{O}_8 + 1/6 \text{O}_2$

M0	sample initial weight	mg
Mt	sample weight	mg
TEMP	temperature	K

Alpha _i	conversion rate - reaction n°i	
k0 _i	pre-exponential factor - reaction n°i	s-1
k _i	kinetic constant - reaction n°i	s-1
v _i	reaction rate - reaction n°i	s-1
Ea _i	activation energy - reaction n°i	J/mol

MMeau	Molar weight of water	MMeau = 18 g/mol
MMdihy	Molar weight of $\text{UO}_3 \cdot 2\text{H}_2\text{O}$	MMdihy = 322 g/mol
MMU3O8	Molar weight of U_3O_8	MMU3O8 = 842 g/mol

Pourcent	Weight loss percent	
M_HYD2	Weight of $\text{UO}_3 \cdot 2\text{H}_2\text{O}$	mg
M_HYD1	Weight of $\text{UO}_3 \cdot \text{H}_2\text{O}$	mg
M_HYD08	Weight of $\text{UO}_3 \cdot 0.8\text{H}_2\text{O}$	mg
M_U3O8	Weight of U_3O_8	mg
M_UO3	Weight of UO_3	mg

dX/dt	time differential of X
-------	------------------------

Equations

Kinetic

$$\begin{aligned}v_1 &= k_1 * (1 - \text{Alpha}_1) \\v_2 &= k_2 * (\text{Alpha}_1 - \text{Alpha}_2) \\v_3 &= k_3 * (\text{Alpha}_2 - \text{Alpha}_3) \\v_4 &= k_4 * (\text{Alpha}_3 - \text{Alpha}_4)\end{aligned}$$

$$\begin{aligned}d\text{Alpha}_1/dt &= v_1 \\d\text{Alpha}_2/dt &= v_2 \\d\text{Alpha}_3/dt &= v_3 \\d\text{Alpha}_4/dt &= v_4\end{aligned}$$

$$\begin{aligned}(\log(k_1) - \log(k0_1)) &= Ea_1/(R*TEMP) \\(\log(k_2) - \log(k0_2)) &= Ea_2/(R*TEMP) \\(\log(k_3) - \log(k0_3)) &= Ea_3/(R*TEMP) \\(\log(k_4) - \log(k0_4)) &= Ea_4/(R*TEMP)\end{aligned}$$

Mass balance

$$\begin{aligned}r1 * \text{MMdihy} &= \text{MMeau} \\r2 * \text{MMdihy} &= \text{MMU3O8}\end{aligned}$$

$$\begin{aligned}\text{pourcent} * m0 &= -100 * (m0 - Mt) \\Mt &= M_HYD2 + M_HYD1 + M_HYD08 + M_UO3 + M_U3O8\end{aligned}$$

$$\begin{aligned}M_HYD2 &= m0 * (1 - \text{Alpha}_1) \\M_HYD1 &= m0 * (\text{Alpha}_1 - \text{Alpha}_2) * (1 - r1) \\M_HYD08 &= m0 * (\text{Alpha}_2 - \text{Alpha}_3) * (1 - 1.2*r1) \\M_UO3 &= m0 * (\text{Alpha}_3 - \text{Alpha}_4) * (1 - 2*r1) \\M_U3O8 &= m0 * \text{Alpha}_4 * r2/3\end{aligned}$$

APPENDIX 7**COMPARISON CURVES : RUNS USED IN IDENTIFICATION**

Weight loss in percent

ES01 : Temperature ramp of 5 C/mn

Weight loss in percent

ES08 : Temperature dwell at 105 C

Weight loss in percent

ES12: Temperature dwell at 250 C

RESEAU EURISYS

Type Doc.	Activité	Cat.MT	N° d'ordre	Révision
NT	10510	00	0004	Rév. A

Page : 57 / 74

APPENDIX 8

COMPARISON CURVES - RUNS CARRIED OUT WITH MOISTURE
ATMOSPHERE

Model with optimized parameters

85

APPENDIX 9**WEIGHT SPECIES VARIATION**

Weight species variation vs time

Weight species variation vs time

ES10: temperature dwell at 75 C

Weight species variation vs time

APPENDIX 10

**X-RAY DIFFRACTION PATTERN RUN ES08 AND ES12 (AFTER
1H30MN OF HEATING TIME)**

ES12
X-ray pattern after heating time of 1h30mn

APPENDIX 11

**PREDICTED MAAS LOSS IN HEATING CONDITIONS OF ICE
CANISTER SLUDGE 96-08 (RUN 46 OF 110)**

APPENDIX 12**PARTICULE-SIZE DISTRIBUTION OF THE TWO SAMPLES**

Imputation : SGN 063
 Echantillon : $\text{UO}_3 \cdot 2 \text{H}_2\text{O}$ (immersion) produit 1
 Commentaires :

Opérateur : BO
 Date de réception : 09/09/97
 Date d'analyse : 14/10/97

Voie Liquide
 Gamme : 0.05 à 900 μm
 Théorie : Mie
 Indice de réfraction de l'échantillon : 1.5295, 0.1000
 Indice de réfraction du dispersant : 1.3300

Dispersant : Eau
 Type de résultat : Volume

Analyse : Polydisperse

Résultat d'analyse :
 Fichier : C:\SIZERS\DATA\UO₃
 N° Enregistrement : 3 > $\text{UO}_3 \cdot 2 \text{H}_2\text{O}$ synt. eau

Diamètre à 50 % : 1.05 μm
 Diamètre à 10 % : 0.26 μm
 Diamètre à 80 % : 14.75 μm

Obscurité : 27.30 %
 Uniformité : 1225.11 %
 Résiduel : 0,9219 %

Imputation: SCN 063

Fichier : C:\SIZERS\DATA\UO3

N° Enregistrement : 3>UO3,2H2O synt. eu

Commentaires:

Opérateur: BO

Date de réception : 9/09/97

Date d'analyse : 14/10/1997

Echantillon : UO3,2H2O :

Produit 1

Voie Humide: pompe:80%, agitation:80%, US:0%.

Opérateur :BO (date :14/10/1997 15:34)

Limites de la tranche (µm)		Fréquence %	Passant %	Limites de la tranche (µm)		Fréquence %	Passant %
0.05	0.06	0.01	0.01	6.63	7.72	0.58	78.26
0.06	0.07	0.02	0.02	7.72	9.00	0.49	78.75
0.07	0.08	0.04	0.06	9.00	10.48	0.36	79.11
0.08	0.09	0.08	0.14	10.48	12.21	0.36	79.47
0.09	0.11	0.18	0.32	12.21	14.22	0.41	79.89
0.11	0.13	0.35	0.68	14.22	16.57	0.52	80.40
0.13	0.15	0.68	1.36	16.57	19.31	0.66	81.07
0.15	0.17	1.21	2.57	19.31	22.49	0.85	81.92
0.17	0.20	1.96	4.53	22.49	26.20	1.06	82.98
0.20	0.23	2.92	7.44	26.20	30.53	1.27	84.25
0.23	0.27	3.95	11.40	30.53	35.56	1.47	85.72
0.27	0.31	4.75	16.15	35.56	41.43	1.64	87.36
0.31	0.36	5.03	21.18	41.43	48.27	1.76	89.12
0.36	0.42	4.88	26.06	48.27	56.23	1.82	90.94
0.42	0.49	4.63	30.69	56.23	65.51	1.81	92.75
0.49	0.58	4.33	35.02	65.51	76.32	1.73	94.48
0.58	0.67	3.93	38.95	76.32	88.91	1.57	96.04
0.67	0.78	3.73	42.68	88.91	103.58	1.33	97.38
0.78	0.91	3.78	46.47	103.58	120.67	1.04	98.42
0.91	1.05	3.89	50.35	120.67	140.58	0.76	99.18
1.05	1.24	4.03	54.39	140.58	163.77	0.50	99.68
1.24	1.44	4.11	58.49	163.77	190.80	0.26	99.94
1.44	1.68	3.90	62.40	190.80	222.28	0.06	100.00
1.68	1.95	3.42	65.82	222.28	258.95	0.00	100.00
1.95	2.28	2.87	68.69	258.95	301.68	0.00	100.00
2.28	2.65	2.31	71.00	301.68	351.46	0.00	100.00
2.65	3.09	1.80	72.80	351.46	409.45	0.00	100.00
3.09	3.60	1.32	74.12	409.45	477.01	0.00	100.00
3.60	4.19	1.10	75.23	477.01	555.71	0.00	100.00
4.19	4.88	0.95	76.18	555.71	647.41	0.00	100.00
4.88	5.69	0.82	77.00	647.41	754.23	0.00	100.00
5.69	6.63	0.69	77.69	754.23	878.67	0.00	100.00

Distribution granulométrique Granulomètre laser

Imputation : SGN 063

Echantillon : $\text{UO}_3 \cdot 2 \text{H}_2\text{O}$ (air humide) produit 2

Commentaires :

Opérateur : BO

Date de réception : 09/09/97

Date d'analyse : 14/10/97

Voie Liquide

Gamme : 0.05 à 900 μm

Théorie : Mie

Indice de réfraction de l'échantillon : 1.5295

Indice de réfraction du dispersant : 1.3300

Pompe : 0.000 l/sec

Dispersant : Eau

Type de résultat : Volume

Agitation : 0.00 Tr/min

Ultrason : 0.00 Watt

Analyse : Polydisperse

Pause US : 0.00 sec

Résultat d'analyse :

Fichier : C:\SIZERS\DATA\UO₃N° Enregistrement : 2 > $\text{UO}_3 \cdot 2 \text{H}_2\text{O}$ synt. eau

N° de série de balayages : 1

Diamètre à 50 % : 193.51 μm Diamètre à 10 % : 12.90 μm Diamètre à 80 % : 395.40 μm

Obscurité : 18.27 %

Uniformité : 80.05 %

Résiduel : 0,3788 %

Type Doc.	Activité	Cat.MT	N° d'ordre	Révision
NT	10510	00	0004	Rév. A

Page : 74 / 74

Imputation: SCN 063

Fichier : CASIZERS\DATA\UO3

N° Enregistrement : 2>UO3,2H2O air humide

Commentaires:

Opérateur: BO

Date de réception : 9/09/97

Date d'analyse : 14/10/1997

Echantillon : UO3,2H2O air humide

Produit 2

Vole Humide: pompe:80%, agitation:80%, US:0%.

Opérateur :BO (date :14/10/1997 15:34)

Limites de la tranche (µm)		Fréquence %	Passant %	Limites de la tranche (µm)		Fréquence %	Passant %
0.05	0.06	0.01	0.01	6.63	7.72	0.49	8.09
0.06	0.07	0.01	0.02	7.72	9.00	0.52	8.61
0.07	0.08	0.03	0.05	9.00	10.48	0.56	9.17
0.08	0.09	0.04	0.09	10.48	12.21	0.60	9.77
0.09	0.11	0.07	0.17	12.21	14.22	0.65	10.42
0.11	0.13	0.12	0.28	14.22	16.57	0.72	11.14
0.13	0.15	0.18	0.46	16.57	19.31	0.80	11.94
0.15	0.17	0.25	0.71	19.31	22.49	0.90	12.83
0.17	0.20	0.33	1.04	22.49	26.20	1.02	13.85
0.20	0.23	0.42	1.46	26.20	30.53	1.16	15.01
0.23	0.27	0.48	1.94	30.53	35.56	1.33	16.34
0.27	0.31	0.51	2.46	35.56	41.43	1.51	17.85
0.31	0.36	0.49	2.95	41.43	48.27	1.72	19.57
0.36	0.42	0.43	3.38	48.27	56.23	1.94	21.51
0.42	0.49	0.36	3.74	56.23	65.51	2.20	23.70
0.49	0.58	0.28	4.02	65.51	76.32	2.48	26.18
0.58	0.67	0.20	4.22	76.32	88.91	2.81	28.99
0.67	0.78	0.14	4.36	88.91	103.58	3.18	32.17
0.78	0.91	0.13	4.48	103.58	120.67	3.60	35.76
0.91	1.06	0.12	4.61	120.67	140.58	4.06	39.83
1.06	1.24	0.13	4.73	140.58	163.77	4.57	44.39
1.24	1.44	0.14	4.87	163.77	190.80	5.10	49.50
1.44	1.68	0.15	5.01	190.80	222.28	5.65	55.15
1.68	1.95	0.16	5.17	222.28	258.95	6.18	61.33
1.95	2.28	0.17	5.35	258.95	301.68	6.69	68.02
2.28	2.65	0.20	5.54	301.68	351.46	6.83	74.85
2.65	3.09	0.23	5.77	351.46	409.45	6.63	81.48
3.09	3.60	0.27	6.05	409.45	477.01	6.04	87.52
3.60	4.19	0.32	6.37	477.01	555.71	5.04	92.57
4.19	4.88	0.37	6.73	555.71	647.41	3.79	96.35
4.88	5.69	0.41	7.15	647.41	754.23	2.48	98.83
5.69	6.63	0.45	7.60	754.23	878.67	1.17	100.00

DISTRIBUTION SHEET

To	From	Page 1 of 1
Distribution	SNF Characterization Project	Date 02/18/98
Project Title/Work Order		EDT No. 620800
Thermal Decomposition of $UO_3 \cdot 2H_2O$, Rev. 0		ECN No.

Name	MSIN	Text With All Attach.	Text Only	Attach./ Appendix Only	EDT/ECN Only
------	------	-----------------------------	-----------	------------------------------	-----------------

Fluor Daniel Hanford, Inc.

R. L. McCormack R3-86 X

B&W Protec, Inc.

T. L. Welsh T4-40 X

Duke Engineering & Services Hanford, Inc.

R. B. Baker H0-40 X
 L. D. Bruggeman H0-40 X
 J. Perez-Carter H0-40 X
 D. R. Duncan R3-86 X
 J. R. Frederickson R3-86 X
 L. H. Goldmann R3-86 X
 L. A. Lawrence H0-40 X
 B. J. Makenas (2) H0-40 X
 R. P. Omberg H0-40 X
 W. H. Rasin R3-11 X
 A. M. Segrest R3-13 X
 D. J. Trimble H0-40 X
 J. H. Wicks R3-11 X
 SNF Project File R3-11 X

Fauske & Associates

M. G. Plys S7-14 X

Fluor Daniel Northwest

R. D. Crowe R3-26 X

Numatec Hanford Corporation

G. P. Chevrier R3-86 X
 T. A. Flament (2) R3-86 X
 C. R. Miska R3-86 X
 C. Pili-Vincens R3-86 X
 J. P. Sloughter H5-49 X

Pacific Northwest National Laboratory

J. Abrefah P7-27 X
 S. C. Marschman P7-27 X

Central Files B1-07 X