Report Title:

Production and Screening of Carbon Products
Precursors from Coal

Carbon Products Consortium

Report Type:

QUARTERLY

Reporting Period Start Date: 07/01/1996 End Date: 09/30/1996

Principal Author(s): John Zondlo
Al Stiller

DOE/PC/94063--T7

Carl Irwin, Program Director

RECEIVED

FEB 07 1997

OSTI

Report Issue Date: 10/25/1996

DOE Award No.: DE- AC22 -95PC94063

Submitting
Organization(s)

West Virginia University Research Corporation
on behalf of West Virginia University

Name & Address

617 N. Spruce Street
Morgantown, WV 26506

(1)

(2)

(3)

(4)

MASTER

(5)

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TABLE OF CONTENTS

Executive Summary	1
1.0 <u>Project Planning and Administration</u>	1
2.0 <u>Consortium Administration and Reporting</u>	1
3.0 <u>Coal Extraction</u>	2
4.0 <u>Technical/Economic Evaluation of WVU Extraction Process</u>	2
5.0 <u>Technology Transfer</u>	3

LIST OF ATTACHMENTS (not on disk)

Attachment 1

**The Future of Carbon Products for Heavy Vehicle Applications
Summary of Workshop Participants**

Attachment 2

**Preliminary Report on the Top Priority R&D Projects Recommended by the Five
Breakout Groups**

Attachment 3

**Coal Precursors for Production of Carbon & Graphite Products
Final Report**

Attachment 4

**Production of Aluminum Reduction Electrodes from Solvent-Extracted Coal-Derived
Carbon Feedstocks
Final Report**

Attachment 5

**Development of Carbon-Carbon Composites from Solvent Extracted Pitch
Final Report**

Attachment 6

Evaluation of Pitches and Cokes from Solvent-Extracted Coal Materials

Executive Summary

This quarterly report covers activities during the period from July 1, 1996 through September 30, 1996. The first year of the project ended in February, 1996; however, the WVU research effort continued through August 14, 1997 on a no-cost extension of the original contract. PETC chose to exercise the option for continuation of the projects and \$100,000 became available on August 9, 1996. The objective for year two is to focus on development of those carbon products from coal-based solvent extract precursors which have the greatest possibility for commercial success.

1.0 Project Planning and Administration

The purpose of Task 1.0 is to prepare and submit to the DOE, a Project Management plan for the WVU portion of the Carbon Products Consortium (CPC) workplan. This Management Plan was submitted to PETC on July 2, 1995. It has been accepted by the COTR and by the contracts management staff. A work plan for year 2 of the project is being developed.

2.0 Consortium Administration and Reporting

The purpose of Task 2.0 is to establish a Participants Agreement (PA) and a Proprietary Information Agreement (PIA) for members of the CPC, to facilitate communications between CPC participants and the COTR, and to help secure, maintain and manage CPC funds obtained under this contract.

The PA and the PIA were finalized on September 1, 1995. It was necessary to revise the PA to define the category of Affiliated Participant for an organization which does not sign the PA or the PIA, but is involved with the work of the CPC. A copy of the revised PA was included with Monthly Status Report No. 8, September 1, 1995 - September 30, 1995.

All monthly status and quarterly technical reports have been submitted as required by the contract. In addition to the required reports, regular communications with the COTR have been maintained.

Extensive efforts have been made to maintain funding through Fossil Energy, as well as, to broaden the base of funding for the work of the CPC. Programs are under development with the Office of Heavy Vehicle Technologies, the Office of Industrial Technologies, as well as, with the Navy Surface Warfare Center.

A copy of the final reports submitted to ORNL by UCAR, ALCOA, FMI, and Koppers are included as attachments to this report. Hard copies mailed under separate cover.

3.0 Coal Extraction

Under Task 3.0 and subtasks, WVU will provide a variety of types and sizes of samples of coal extracts to the industrial and national laboratory participants. In addition, green and calcined cokes will be developed. A summary of technical developments and other activities follow:

A capillary rheometer was acquired from Amoco Polymers and is now rebuilt and operational. This apparatus will allow us to evaluate the viscosity of the coal-derived pitches over a wide range of temperatures and rheometer. Currently, standard viscosity fluids are being tested and the instrumental is being calibrated. Work will soon commence on the rheologic characterizations of hydrogenated coal extracts. It should be noted that this apparatus will also give us the capability of spinning fibers out of the various coal-derived pitches.

Considerable effort has gone into replenishing our supply of coal-derived pitches. Extracts from both raw coal as well as hydrogenated coal have been prepared and stock-piled. The goal here is to make enough pitch so that Koppers and Alcoa will have quantities sufficient to construct a small-scale carbon anode for evaluation. Discussion is underway as to the best way to proceed in the next but smaller phase of the PETC contract.

A subcontract to WVU on AMOCO's NSWC project was in progress during the reporting period. Specifications for pitch precursors for high-thermal conductivity fibers have been received from AMOCO and WVU laboratory equipment has been assembled.

Discussions are taking place between BASF, Koppers and WVU as to the best way of proceeding toward a small-scale pilot demonstration unit. Negotiations are on-going and hopefully some agreement can be reached soon.

WVU has developed reactor systems to produce larger samples of carbon foams and is currently in full production of small test specimens. Evaluation of these specimens is being carried out at the NASA Langley Research Center. The coal-based carbon foam technology was developed concurrently with the CPC program. Coal-based carbon foam samples for testing have been produced with various precursors and with various additives. For example, inexpensive chopped fibers supplied by AMOCO have been added to the foam precursor to increase the strength of the resulting foam.

WVU is in the process of submitting a proposal to the Army Tank Command with our CPC affiliate, FMI. The proposal is in response to a BAA for improved vehicular structural materials.

4.0 Technical/Economic Evaluation of WVU Extraction Process

WVU provided all requested information to the MITRE Corporation for their economic analysis of the coal extraction process. A draft of the MITRE report was received in mid July,

1995 and a revised version was received in September, 1995.

The MITRE report suggests several process changes whose implementation on a larger scale could substantially reduce the cost of the coal extraction process. MITRE finds that coal extract based calcined coke for anodes could be produced for approximately \$177 per ton. A February 1 article in the Financial Times reported that world aluminum production could be restricted by shortages of petroleum coke. The article said that coke prices have doubled the past year to between \$240 and \$250 a ton. This is because it is more profitable for refineries to make liquids than coke. MITRE also recommends research on the production of isotropic carbon fibers from coal extracts of unhydrogenated coal. Such fibers are in the \$8 to \$10 per pound range and the market for low cost fibers is expected to double in the near future.

5.0 Technology Transfer

A confidentiality agreement between BASF, Koppers and WVU is being negotiated. The agreement will facilitate discussions on scaling up production of certain types of coal-based extracts for further evaluation. BASF makes the solvent NMP which is used in the WVU coal extraction process.

The workshop on carbon products and heavy vehicles was held September 4 and 5 in Chicago. Approximately 75 attendees representing 38 companies, four universities, seven U.S. government agencies and one Netherlands government agency were at the workshop. See the attached participant summary. A copy of the priority R&D topics reported by the five breakout groups is attached to this report. A copy of the presentation material from the speakers and panelists is available.

WVU will schedule a CPC business meeting and project review for the week of November 18, 1996. A portion of the time will be devoted to developing a vision statement with the U.S. DOE Office of Industrial Technologies on the role of carbon products in their Industries of the Future Program.

Chicago
The Future of Carbon Products for Heavy Vehicle
Applications

Summary of Workshop Participants

GOVERNMENT AGENCIES

Argonne National Laboratory
 • Energy Technology Division
 Lawrence Livermore National Lab
 • Mechanical Engineering Dept.
 • Transportation Program
 NASA-Langley Research Center
 • Materials Division
 NREL
 ORNL
 • Automotive Composites Research
 • Carbon & Insulation Materials
 Technology Group
 • Center for Composites Manufacturing
 Technology
 • Metals & Ceramics Division
 • Transportation Technologies
 U.S. Department of Commerce
 • NIST
 U.S. DOE
 • Office of the Deputy Secretary
 • OHVT
 -Transportation Technologies
 -Heavy Vehicle Systems Technology
 NOVEM (Netherlands)

PRIVATE INDUSTRY

American Bus Association
 American Sightseeing
 American Trucking Associations
 AMOCO Polymers, Inc.
 Applied Sciences
 Battelle
 Ciba Polymers
 CONOCO
 Dana Corporation
 DFI Pultruded Composites
 Dorsey Trailers
 Energetics
 Failure Analysis Associates
 Ford Motor Company
 Foster-Miller, Inc.
 GHL
 Grafil, Inc.
 Hexcel
 Hilco Technologies
 Hoosier Tank & Manufacturing
 Kenworth Truck
 Lincoln Composites
 Lockheed Martin Engineering & Sciences
 Mack Trucks
 Monon Corporation
 Motor Coach Industries (Canada)
 Navistar International
 Northrop Grumman Corp.
 Nova Bus, Inc.
 Parish Heavy Truck
 Prevost Car, Inc. (Canada)
 Rockwell International
 Rockwell Science Center
 SACMA
 Tempress
 Trucking Research Institute
 UCAR
 Zoltek Corporation

ACADEMIC

Clemson University
 • Chemical Engineerin
 • Mechanical Engineer
 Penn State University
 • Chemical Engineerin
 Wayne State University
 • Mechanical Engineer
 West Virginia University
 • Chemical Engineerin
 • MAE
 • NRCCE

ATTACHMENT 2

Applications of Carbon Products for Efficient Operation of Heavy Trucks, Buses, and Other Commercial Vehicles

PRELIMINARY REPORT ON THE TOP PRIORITY R&D PROJECTS RECOMMENDED BY THE FIVE BREAKOUT GROUPS

October 19, 1996

Breakout Group A: Body, chassis, cargo area, trailers, seat structures, wheel wells, vehicle interior, frame rails, other structural members.

- A.1.** Grand Challenge Project: Launch a consortium similar to the Automotive Composites Consortium which would take a systems approach to demonstrating step reductions in the final cost of major carbon composite components for heavy vehicles (e.g., a refrigerator trailer or transit bus or transit bus panels built with \$4 per pound carbon/glass composites.)
- A.2.** Develop a computer analysis/design tool and associated material property data base for the heavy vehicle industry that can accommodate hybrid material systems using both glass and carbon fibers, and with the capability to predict fatigue life of composite parts.
- A.3.** Develop frame cross member made with carbon/glass fiber reinforcement as a bolt-in replacement for current steel component on existing heavy vehicle.

Breakout Group B: Crash protection components, energy absorbing materials, bumpers and impact guards (front, rear, and side), vehicle crashworthiness, fire protection components.

- B.1.** Grand Challenge Project: Have better performing, more cost effective energy absorbing/fire protection composite components in production within five years. Application areas of interest include (1) rear impact protection, (2) frontal aggressivity, (3) fuel tank fairings and fuel tank fire retardation, (4) cab occupant protection, (5) side underride protection.
- B.2.** Incorporate existing aerospace technologies and materials to demonstrate feasibility of composite parts on heavy trucks and buses, including life cycle costs, comparison with others materials, etc.
- B.3.** Develop coal-derived, cost effective materials such as carbon foams and fibers which meet or exceed the life-cycle costs of existing materials.

Breakout Group C: Running gear: brakes, clutches, suspension, axles, wheels, steering components.

- C.1.** Grand (General) Challenges (for carbon products): Reduce material and manufacturing costs while improving quality assurance. Develop design tools/methodology and

testing/validation procedures.

- C.2. Develop improved, cost competitive, carbon-based brake friction materials carbon composite pads and rotors that meet/exceed current materials properties. Build on experience of aerospace industry.
- C.3. Develop reduced rolling resistance tires made with nanofibers and/or long chain carbon black for improved fuel economy. (10% reduction in rolling resistance yields 5%-7% increase in fuel economy.)

Breakout Group D: Powertrain: engine components, drive shafts, radiators, transmissions.

- D.1. Grand Challenge Project: Demonstrate feasibility of producing carbon-carbon engine components such as pistons, valves, cylinder liners, engine blocks, turbocharger scrolls, and exhaust manifolds. Ultimate goal is a single cylinder "all composite" engine which operates at near adiabatic conditions.
- D.2. Investigate heavy vehicle cooling systems based on the use of selectively placed, high thermal conductivity carbon fibers (heat pipes) in the engine blocks.
- D.3. Design and construct a full-scale composite driveshaft which incorporates a combination of glass and carbon fiber reinforcement. Special attention must be given to end couplings.
- D.4. Evaluate use of carbon foam as filler/spacer material in sandwich structures.
- D.5. Other product development ideas: train/electrical actuators, connecting rods/wrist pins, shift lever, low heat loss manifold, catalyst support/particulate traps, bushings/bearings.

Breakout Group E: Fuel/Air systems: Tanks, seals, carbon adsorbents, high temperature filters, carbon materials compatibility with diesel and alternative fuels, thermal/mechanical cycle fatigue.

- E.1. Grand Challenge Project: Develop low pressure (500 psi or less) adsorption storage of NG on activated carbon/carbon fibers with tank capacity equivalent to 3,600 psi storage tanks. Release of stored gas is an R&D issue.
- E.2. Characterize and utilize low-cost and coal-based fibers for fabrication of CNG tanks and other applications.
- E.3. Develop improved seals and polymeric fuel lines with addition of vapor grown carbon fibers or carbon solids.
- E.4. Conduct technical and economic feasibility study of cryogenic ($T = -260$ deg F, $P = 150$ psi) storage tank and associated fuel systems for LNG fueled heavy vehicles.
- E.5. Determine feasibility of carbon foam/carbon fiber particulate traps for diesel exhaust and fugitive emissions.
- E.6. Determine feasibility of using oriented high thermal conductivity carbon devices for removal of heat from engines, brakes, etc.

COAL PRECURSORS FOR PRODUCTION OF CARBON AND GRAPHITE PRODUCTS

FINAL REPORT

April 8, 1996

Research Sponsored by the U.S. Department of Energy,
Office of Fossil Energy
Advanced Research and Technology Development Materials Program

Report Prepared by
I. C. Lewis, R. T. Lewis, and H. K. Mayer
UCAR CARBON COMPANY INC.
Parma Technical Center
P. O. Box 6116
Cleveland, Ohio 44101

under Subcontract 62X-SR928C, WBS Element-UCAR-3

for
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831
Managed by
LOCKHEED MARTIN ENERGY RESEARCH CORPORATION
for the
U.S. DEPARTMENT OF ENERGY
under contract DE-AC05-96OR22464

I. SUMMARY

Chemical and analytical characterization data were obtained for NMP extracts of hydrotreated coal prepared by the West Virginia University (WVU) Group. Initial evaluation of small-scale samples produced by varying coal hydrotreating time, temperature, and catalyst type were used to define the conditions that would produce material suitable as binder, impregnant, C/C matrix pitches and precursors for needle coke, anode coke, and mesophase pitch fibers. In addition to analytical characterization, mesophase formation studies were used to assess the coal extract quality.

Based on the small-scale testing, specific extracts derived from hydrotreating coal at 450°C were recommended for scaleup. Evaluation of the 450°C - 2-hour hydrotreated coal extract showed that it should be suitable as an impregnant or binder pitch and as a precursor for needle coke and mesophase pitch. This material formed a large-domained mesophase, despite a high oxygen and nitrogen content.

A small graphite artifact was produced using coke derived from the extract as the filler and the extract itself as the binder. The coefficient of thermal expansion (CTE) of $0.26 \times 10^{-6}/^{\circ}\text{C}$, measured for the artifact is in the range found for electrode type graphite.

Coal extraction residues were steam activated to produce active carbons with surface areas from 400-700 m²/gm. The program has demonstrated that the coal extraction process coupled with hydrotreatment, has the potential for providing a broad range of carbon and graphite products.

II. INTRODUCTION

The main goal of the overall program on "Coal-Based Precursors for Carbon Products" was to demonstrate the utility of coal extracts from the WVU extraction process as suitable base raw materials for the carbon products encompassed by the Carbon Products Consortium (CPC) team. These include binder and impregnating pitch, coke for graphite electrodes, cokes for anodes and specialty graphite, matrices for C/C composites and raw material for mesophase pitch fibers. Each of these products has unique requirements for properties of a suitable precursor. Our previous work on the Coal Precursor for Graphite Program⁽¹⁾ has shown that the WVU coal extraction process coupled with hydrotreatment, does have the potential for achieving this objective. Our current effort, therefore, involved the screening and evaluation of extracts produced by the WVU Group and recommending appropriate materials for scaleup for subsequent evaluation by Consortium Team members.

Our program involved an initial characterization of small-scale extracts using standard analytical methods and mesophase formation studies. This was followed by feedback to the WVU Group and to the CPC partners (Koppers, ALCOA, FMI, and APPI) with recommendation of material for scaleup. We also performed similar analytical and mesophase studies on some of the scaled-up extracts.

As part of our program, we investigated the activation of the coal extraction residues for the purpose of producing a useful active carbon. A further task, which was started towards the end of the program, was to fabricate a small graphite artifact using coke derived from coal extract as the filler and the coal extract itself as a binder. The results of our studies are summarized in the following sections of this report.

III. EXPERIMENTAL PROCEDURES

A. Analytical Methods

1. Elemental Analysis - Elemental C, H, N, and O data were measured using a LECO CHN 1000 Analyzer. Elemental sulfur was measured using a LECO SC-132 carbon analyzer.
2. Thermogravimetric Analysis (TGA) - The data were obtained using TA Instruments 951 TGA module. Samples were heated at a rate of 10°C/minute in an inert atmosphere.
3. Nuclear Magnetic Resonance (NMR) - The NMR spectra were measured for CS₂ solutions using a Varian A-60 spectrometer. In order to increase solubility, the solutions were prepared by either refluxing with solvent or by ultrasonic mixing.
4. Toluene and Trichlorobenzene (TCB) Solubility - The insoluble contents in toluene and TCB were determined using procedures in ASTM D-4072.
5. Mettler Softening Point (SP) - The softening points were measured using a Mettler FP83HT SP apparatus following the standard procedures in ASTM D-3104.
6. Modified Conradson Carbon (MCC) - The MCC data (carbon yields) were obtained using procedures in ASTM D-2146.
7. Gel Permeation Chromatography (GPC) - Molecular weight determinations were obtained from GPC measurements using a Dupont 850 Liquid Chromatographic System coupled with a Knauer High Temperature Differential Refractometer. The column configuration and calibration have been described elsewhere⁽²⁾. The GPC data were obtained for the portion soluble in TCB solvent at 90°C.

B. Mesophase Formation Studies

1. Test-Tube Evaluations

The small-scale extracts were evaluated initially for mesophase quality by heating 0.7-1.3 gm samples in pyrex test tubes for six hours at 400°C in an inert gas environment. The objective was to produce a 15-40% mesophase content in the heat-treated residue, with most of the mesophase concentrated at the bottom of the test tube. After heat treatment, the pyrex test tubes were dissolved in aqueous HF, and the residues were mounted and polished by standard metallographic procedures to show a midline vertical cross-section. Polarized light microscopy techniques were used to make a qualitative assessment of the amount and quality of the mesophase and the presence, if any, of insoluble solid contaminants in the extracts.

2. Mesophase Domain Size

Specimens for automated image analysis were prepared by heat treating the coal extracts in an inert atmosphere at 400°C in ceramic boats and then preparing "annealed" samples for the mesophase domain size measurements using procedures described elsewhere⁽³⁾.

3. Hot-Stage Microscopy

Direct observations of the melting behavior, gas evolution characteristics, mesophase formation rate, and mesophase quality were made while heating the coal extracts up to 400°C at 6-10°C/min. and holding at 400°C for several hours. Details of the cover glass "sandwich" configuration used to contain the sample, the modified Kofler hot stage and the polarized light microscope have been reported previously⁽⁴⁾.

A simple CCD video camera and color monitor/VCR system were acquired late in the contract period to facilitate direct recording of the dynamic behavior of the coal extracts when they were heated on the hot-stage microscope.

C. Steam Activations

Activation experiments were carried out on powdered coal extraction residues using a specially designed tumbling furnace. The activations were performed by passing a mixture of steam and N₂ over the sample maintained at a constant temperature of 900°C. The treatment was interrupted intermittently and the sample weighed to determine percent burn-off.

D. Graphite Fabrication

Small 19mm-diameter graphite electrodes were fabricated using calcined coke produced from hydrotreated coal extract as filler and the hydrotreated extract as the binder. The binder and filler were mixed and extruded using standard procedures. The formed rods were then baked and graphitized to 3,000°C.

IV. EXPERIMENTAL RESULTS

A. Small-Scale Coal Extracts

1. Sample Preparations

The WVU Group initially carried out a series of small-scale extractions on a hydrotreated bituminous coal, WVGS-13421. The coal was hydrotreated at three different temperatures 350°C, 400°C, and 450°C for a period of 1 hour in 800 psig H₂. An additional set of hydrotreatments was carried out at 450°C for 2 hours. For each temperature, the hydrotreatments were performed using tetralin as a hydrogen donor without a catalyst, and with the use of a Fe₂S₃ catalyst or a sulfided Mo catalyst. The NMP extractions were performed on the hydrotreated products.

Initial characterization data from the WVU Group showed that the softening temperatures of the 350°C and 400°C extracts were much too high to make them useful for most of the proposed applications of the Team. We therefore agreed to fully characterize only the 450°C-treated materials.

Our characterization results for the extracts from the WVGS-13421 coal hydrotreated at 450°C for 1 and 2 hours follow.

2. Analytical Characterization of 450°C - 1-Hour Samples

The analytical characterization data for the 3 different materials prepared from hydrotreated coal at 450°C for 1 hour are presented in Table I. The Mettler softening points (measured at WVU) range from 156° to 190°C which are too high for use as conventional binder and impregnant pitches.

Table I
Characterization Data for Extracts from Hydrotreated Coal, WVGS-13421, 450°C - 1 Hour

	C-269-2 Thermal	C-279-1 Fe₂S₃	C-288-2 Mo(S)
SP°C	190	156	158
%C	85.2	84.5	81.9
%H	5.51	5.63	5.82
C/H atomic ratio	1.30	1.26	1.18
%N	3.08	2.89	3.73
%O	4.73	4.60	6.07
%S	0.49	0.57	0.43
TGA Yd%	49	46	42
%TI	28.9	-----	-----
%Arom. H.	38	36	33
GPC - MW (Mn)	415	395	371
%TCB Insoluble	40.6	26.0	19.7
%NMP	0	0.1	5

All the extracts show very high N and O contents. The Mo(S)-treated coal extract showed the highest N content as a result of retained NMP. The low C/H ratios are expected for the hydrotreated extracts.

The proton NMR spectra obtained in CS₂ solution are presented in Figures 1-3. The extracts were incompletely soluble in CS₂. We were able to obtain essentially complete solution in pyridine D-5; however, the residual hydrogen or water in the solvent interfered with the analysis. The extracts all show extremely high aliphatic hydrogen contents resulting from the hydrogenation of aromatic rings. The NMR results are also summarized in Table I. For comparison, a spectrum for coal tar binder pitch exhibits about 85% aromatic hydrogen compared to the 33-38% range for the extracts. From the NMR data as well as the C/H ratios, it appears that the catalytically treated materials may have been slightly more hydrogenated.

The TGA data for the 3 extracts are presented in Figures 4-6. The TGA carbon yields of 42-49% are quite acceptable for a pitch-type material. The low-temperature weight loss occurring from about 150-250°C is attributed to evolution of retained NMP solvent. This is particularly apparent in the TGA result for the Mo(S) product in Figure 6.

The GPC curves for the three 450°C - 1-hr. samples are shown in Figures 7-9. They are all similar, except for a resolved doublet in the Fe₂S₃

catalyzed material. They all show a broad symmetrical molecular weight distribution (MWD) with an apparent molecular weight range of about 250-900. The negative peaks in the GPC spectra are attributed to retained NMP. An estimate of the amount of NMP present was made by integrating these peaks and the results are summarized in the last line of Table I. Also shown in Table I are the toluene insolubles (TI) content and the measured insolubles in TCB.

3. Analytical Characterization of 450°C - 2-Hour Samples

The analytical data for the small-scale extracts obtained from coal hydrotreated at 450°C for 2 hours are summarized in Table II. The softening points are all considerably lower than those for the samples produced by hydrotreating for 450°C for 1 hour. Like the 450°C - 1-hour samples, the products in Table II exhibit very high N and O contents. The H contents, however, are higher, for the 2-hour samples reflecting the greater degree of hydrogenation. The 2-hour materials also showed a higher solubility in TCB than the 1-hour samples.

Table II
Characterization Data for Extracts from Hydrotreated Coal,
WVGS-13421, 450°C - 2 Hours

	C-300-3 Thermal	C-300-6 Fe₂S₃	C-300-9 Mo(S)
SP°C	126	123	131
%C	84.2	83.9	86.1
%H	5.74	5.75	5.82
C/H atomic ratio	1.23	1.23	1.27
%N	3.65	3.60	3.22
%O	5.53	5.66	4.61
%S	0.35	0.42	0.41
TGA Yd%	40	41	42
%Arom. H	40	40	43
GPC - Mn	421	426	416
%TCB Insoluble	21.9	22.3	18.1
%NMP	2	2	1

The proton NMR data for the extracts in Figures 10-12 show a lower content of long chain aliphatic protons than for the 1-hour treated samples, indicative of more selective hydrogenation of aromatic rings. The TGA results in Figures 13-15 demonstrate a reduced carbon yield for the

450°C - 2-hour materials as compared to the 1-hour samples. The presence of retained NMP is evident from the weight loss occurring below 300°C. The GPC curves for the 450°C - 2-hour samples in Figures 16-18 exhibit somewhat broader MWD's when compared to the 1-hour extracts, which could account for the lower softening points. The amounts of NMP solvent present in the extracts, as measured from integrating the negative GPC peaks, are also summarized in Table II. From the measured properties, there appears to be no advantage for the use of a catalyst during the hydrotreatment.

4. Mesophase Formation Studies of 450°C - 1-Hour and 2-Hour Samples

Hot-stage microscopy examinations were carried out on all three of the small-scale 450°C - 1-hour samples. The primary results from the heat-up and hold period at 400°C are summarized in Table III. The initial softening temperatures from visual observations on the hot-stage were reasonably consistent with the Mettler S. P. results in Table I. The most unusual feature of the hot-stage microscopy observations was the onset of vigorous bubbling, presumably gas evolution, at temperatures in the 250° to 275°C range. Conventional coal tar and petroleum pitches do not show this vigorous bubbling behavior below 300°C. Evolution of residual NMP (202°C Boiling Point) could be responsible for a portion of the low-temperature gas evolution from the extracts, but certainly not all of it, because the vigorous gas evolution continued throughout the 300°-400°C range. Dehydrogenation and/or decomposition reactions are suspected to be the origin of the gas evolution in these initial 450°C - 1-hour extracts, but an attempt to confirm evolution of H₂, H₂O, or other low MW gases in this temperature range was not successful⁽⁵⁾.

Mesophase spheres were detected at the edge of the cover glass sandwich in all three 450°C - 1-hour samples after ~20 min. at 400°C, indicating that all of them had comparable mesophase formation rates. The mesophase viscosity appeared to be reasonably low, based on bubble deformation behavior, and was essentially equivalent in the 3 samples. The overall mesophase quality was estimated to be borderline for a needle coke precursor.

All of the samples contained a small amount of finely divided solids, but none had a concentration judged high enough to have a significant effect on coke quality or performance as an impregnant. However, these finely divided solids would be expected to degrade the performance of these extracts as a mesophase pitch fiber precursor.

All of the 450°C - 1-hour and 450°C - 2-hour samples were evaluated by the test-tube method. Measured yields after heat treatment at 400°C for six hours were in the 72 to 85% range. However, all of these samples foamed extensively during the heat treatment, so some material may have been lost. The extensive foaming during the test-tube heat treatments of the 450°C - 1-hour samples is consistent with the vigorous low-temperature bubbling behavior noted during the hot-stage microscopy observations. The 450°C - 2-hour samples foamed as much as the 450°C - 1-hour samples in the test-tube heat treatments, so the additional reaction time at 450°C did not seem to have any significant effect on this characteristic of the small-scale extracts.

Examination of the domain size in the coalesced mesophase layer, which collects at the bottom of the test tube for conventional coal tar and petroleum pitches, can be used as an indicator of overall mesophase quality. Unfortunately, gas evolution from all of the small-scale extracts was so copious and disruptive that no well-defined coalesced mesophase formed at the bottom of the test tube. The actual appearance of all of the residues from test-tube heat treatments of the extracts is shown schematically in Figure 19. Because of the effects of gas evolution, we were not able to obtain a definitive evaluation of the uniformity and quality of the mesophase formed in the small-scale extract by the test-tube method. However, based on appearance, the overall mesophase quality was judged to be borderline for a needle coke precursor. The true mesophase quality may have been somewhat better, but the effects from the gas evolution precluded obtaining a definitive answer.

Finely divided solids were detected around the perimeter of most of the coalesced mesophase regions and many of the larger mesophase spheres in all of the test-tube residues. These solids provided a local, short-range decrease in the mesophase domain size, but the effect on the overall quality was minor.

Qualitative SEM/EDX analyses were carried out on the finely divided solids in the C-296-2 (Thermal, 450°C - 1-hour) extract. Most appeared to be carbonaceous, some contained high Si, Al, O levels ($\text{SiO}_2 + \text{Al}_2\text{O}_3$?), and some contained high Cu, Fe, S, and O levels (possibly a mixed copper and iron sulfate). The WVU Group suggested that the high Cu content in the last type of solid may have originated via attack of a copper gasket by the hot reactant mixture in the small-scale apparatus.

Table III
Summary of Hot-Stage Microscopy Observations on 450°C - 1-Hour Samples

SAMPLE	INITIAL SOFTENING TEMP., °C	ONSET OF VIGOROUS BUBBLING, °C	INITIAL DETECTION OF MESOPHASE, TIME AT 400°C
C269-2 Thermal	198	255-275	21 min.
C279-1 CF-1, Fe ₂ S ₃	155	250	16
C288-2 CF-2, Mo(S)	125	235	24

B. Large-Scale Extracts from Hydrogenated Coal

1. Sample Preparation

Following our evaluation of the small-scale extracts, we recommended that the 450°C hydrotreated coal materials be scaled up for evaluation by the Team. The extracts produced without the use of any catalyst appeared suitable for testing as a binder and impregnating pitch and as a precursor for needle coke and mesophase pitch for fibers.

Scaleup of the hydrotreated coal extracts was performed at WVU by hydrotreating 600 grams of powdered coal in 1-gallon batch reactors. They investigated 2 different coals using hydrotreatment times of 1 and 2 hours at 450°C. A description of the 4 materials produced (A066, A076, A075, and A073) and the properties measured at WVU are summarized in Table IV. The materials were also vacuum dried for an extended time in order to remove all of the retained NMP. We received about 200 gms of each material for further characterization.

Table IV
Large-Scale, Hydrotreated Coal Extracts

Prepared Conditions	A066 Coal 13421 450°C - 1 hr.	A076 Coal 13421 450°C - 2 hr.	A075 Coal 13423 450°C - 1 hr.	A073 Coal 13423 450°C - 2 hr.
SP, °C	155.8	101.7	129.3	112.5
Density, g/cc	1.264	1.227	1.220	1.223
TI, Wt %	22.3	12.1	19.8	20.9
Coke Yield, Wt %	62.4	54.0	54.7	52.6

2. Analytical Data for Large-Scale 450°C Hydrotreated Coal Extracts

The data and properties obtained for the four large-scale coal extracts are summarized in Table V. We fully characterized the more extensively hydrotreated (2-hour) samples because these had the lowest softening points, making them more suitable for use as binder or impregnating pitch. In general, these larger scale products were superior in behavior to the small-scale samples discussed previously. One major characteristic was the essentially complete absence of any retained NMP. The N and O contents were therefore substantially reduced, but they were still much higher than those found in conventional coal tar pitches. The C/H ratios are similar to those in the comparably treated small-scale extracts.

Only the 2-hour products had softening points in the range of those for conventional carbon binder and impregnant pitches. The carbon yields of 52% for these materials are similar to those for commercial solids-free pitches of comparable softening point.

Table V
Properties of Large-Scale WVU Coal Extracts

	A076 450°C - 2 Hrs. Coal 13421	A066 450°C - 1 Hr. Coal 13421	A073 450°C - 2 Hrs. Coal 13423	A075 450°C - 1 Hr. Coal 13423
SP, °C	104.7	160.7	115.3	134.5
MCC %	52.9	63.0	51.7	53.7
TGA Yd%	34	45	31	36
C, %	88.9	-----	89.6	-----
H, %	5.85	-----	5.78	-----
C/H Ratio	1.28	-----	1.30	-----
N, %	2.20	-----	1.90	-----
O, %	2.74	2.27	2.49	3.33
S, %	0.45	-----	0.33	-----
Ar H %	45	44	48	39
Mn (GPC)	367	417	389	388
Mesophase (μ)	272	166	136	78

The proton NMR spectra for the four materials in Table V are presented in Figures 20-23. All the extracts show substantial contents of hydrogenated ring systems. The decrease in the long chain aliphatic hydrogen peak at about 1.3 ppm, with extended hydrogenation, is particularly noticeable for the WVGs-13423 coal. The TGA curves for these large-scale extracts are shown in Figures 24-27. It is evident that the improved sample-drying procedure has removed any retained NMP. As expected, the total TGA weight losses increase for the more severely hydrotreated samples. The GPC curves for the four materials shown in Figures 28-31 do not exhibit any negative peaks due to NMP. The more severely hydrotreated coals show a broader molecular weight distribution (MWD) and the presence of an unresolved component at 280 a.m.u. when compared to the 1-hour samples.

3. Characterization of Extract Distillation Residues

We also received 3 distillation residues prepared by vacuum stripping of Sample A073 at temperatures of 250°C, 350°C, and 400°C. The materials are described in Table VI. The samples were prepared to determine whether we could detect any chemical changes resulting from heat treating at these temperatures.

Table VI
Vacuum Distillation Residues from Sample A073 (WVGS 13423 - 450°C - 2 Hours)

SAMPLE	DISTILLATION TEMP., °C	YIELD, %
D035-1	250	76
D035-2	350	70
D035-3	400	68

We obtained NMR and TGA data for these residues and the results are summarized in Table VII. The NMR results show an increasing aromaticity with increasing depth of distillation. It is not possible to determine whether this effect is due to removal of volatile hydrogenated components during distillation or to low-temperature cracking reactions. The NMR data for the distillation residues are presented in Figures 32-34 while the TGA data are shown in Figures 35-37.

Table VII
Characterization of Hydrotreated Coal Extract Distillation Residues

SAMPLE	% AROM H	% LONG CHAIN*	TGA Yd. %
D035-1	52	21	43
D035-2	55	22	58
D035-3	60	15	57

* % of aliphatic H that is long chain

4. Mesophase Evaluations of Large-Scale Extracts

Hot-stage microscopy examinations were carried out on both of the 450°C - 2-hour extracts in the same run. The A073 extract began to soften visibly at 94°C, and the A076 extract had slumped noticeably by 104°C while they were being heated at 6°C/min. to 400°C. The low initial visible softening temperatures on the hot-stage are consistent with the low Mettler S. P.'s given in Tables IV and V for these two extracts.

Both of these large-scale extracts evolved much less gas between 250°C -350°C as compared to the levels seen with all of the small-scale extracts. They behaved much more like conventional petroleum and coal tar pitches in their low-temperature gas evolution characteristics. Apparently, the combined effects of more stringent drying conditions to remove residual NMP and the somewhat more severe reaction conditions

employed by the WVU Group for the large-scale extracts had nearly eliminated the severe gas evolution problem detected with the small-scale extracts.

Small amounts of mesophase spheres were detected at the edges of the cover glass sandwiches in both A073 and A076 extracts after ~25 min. at 400°C, indicating that they had comparable initial mesophase formation rates. These onset times are only marginally longer than those noted for the 450°C - 1-hour, small-scale samples.

A hot-stage microscopy run carried out with both of the 450°C - 1-hour samples showed an initial softening temperature of 114°C for A066 extract and 146°C for A075 extract. These results are reasonably consistent with the Mettler S. P. data in Tables IV and V.

The A066 and A075 extracts also evolved much less gas in the 250°-350°C range than the small-scale extracts. Clearly, the beneficial effects from the more stringent drying conditions and the somewhat different reaction conditions employed by the WVU Group were realized after only 1 hour at a nominal reaction temperature of 450°C.

Small amounts of mesophase were detected at the perimeter of the cover glass sandwiches for both A066 and A075 extracts after 21-22 min. at 400°C on the hot-stage microscope. Hence, the mesophase formation rates of these large-scale 450°C - 1-hour samples were comparable to each other and to those for both the 450°C - 1 hour large-scale and small-scale extracts. Both of the 450°C - 1-hour samples appeared to generate slightly more true pyrolysis gas during the hold period at 400°C than the 450°C - 2-hour samples. This is an indication that the 450°C - 1-hour samples had a slightly higher initial rate for cracking reactions.

All of the large-scale extracts were heat treated in boats at 400°C to produce approximately 50% mesophase and then subjected to the "annealing" process for measurement of mesophase domain size. Polarized light (crossed polars) micrographs taken at 50X and 250X magnification of the derived mesophase are shown in Figures 38-41. It is apparent that the more extensively hydrotreated extracts give larger domain size mesophase than the less-treated 1-hour samples. It is also evident that the mesophase derived from the WVGs-13421 coal extract has a larger domain size than that from WVGs-13423 coal for the same hydrotreatment severity. The A076 extract from WVGs coal 13421 hydrotreated 2 hours at 450°C gave the largest mesophase domain size of any of the large-scale extracts. Mesophase domain sizes were obtained by image analysis and are reported in Table V. It is apparent that the domain sizes of the extracts from the

WVGS-13423 coal are significantly smaller than the corresponding extract from the WVGS-13421 coal. The measured domain size of 272 μ m for the A076 extract is in the range found for excellent needle coke precursors.

The presence of solid particles in the coalesced mesophase and at the mesophase/isotropic phase boundary was noted to some extent in the annealed samples from all of the large-scale extracts. The WVGS-13421 extracts had more of this finely divided material than those derived from WVGS-13423. Figure 42 shows an area where the solids have collected or segregated in a small region near the edge of the coalesced mesophase from the A076 extract sample from WVGS-13421. SEM/EDX analyses of the particles in this cluster showed that several different materials were present. Carbonaceous particles with very high C and modest S levels were numerous, presumably coke-like material from the original coal which had not reacted during hydrotreatment. Particles with high Si, Al, and O contents were also prevalent, presumably very small ash particles from the original coal which had not been removed completely during the filtration step after hydrotreatment and NMP extraction. There was also a significant number of particles with high Fe, Cr, S, and possibly O contents, presumably iron and chromium sulfates. A few particles with high Ti and O contents (TiO₂?) or high Cu, K, and small O contents (calcium and potassium sulfides or sulfates?) were also detected. As expected, most of these finely divided solids originate in the coal. Presumably, their removal would be more complete in larger scale equipment.

C. Additional Extract Samples

Small quantities of three additional extract materials were received from the WVU Group toward the end of the contract period. Two of the samples were the toluene soluble (TS) portions from hydrotreated coal extracts. D065-2 was the TS portion from a 450°C - 1-hour hydrotreatment of the WVGS-13423 coal, and D054 was TS from a 450°C - 2-hour hydrotreatment of WVGS-13421 coal. Both of these extracts melted in the 90°-100°C range on the hot-stage microscope and had low yields after heating to 400°C at 6°C/min. Both were also very refractory during the hold period at 400°C and required 1.5-2.0 hours to produce detectable mesophase spheres. An attempt to evaluate their mesophase domain size was unsuccessful because these TS materials were so unreactive under the normal heat treatment conditions and had low yields. The low softening point behavior and low yield upon heat treatment are consistent with the low MW range encompassed by toluene soluble material.

A third extract (A122) was prepared at WVU by carrying out a 450°C - 1-hour hydrotreatment on the toluene insoluble (TI) fraction from a large-scale NMP extract from an initial 450°C - 2-hour hydrotreatment of WVGS-13423 coal. This double-hydrotreated material had an initial softening temperature of 188°C and formed mesophase spheres quite rapidly at 400°C, probably due to distillation of volatiles. Additional mesophase formed at a normal rate for

thermal processing of good feedstocks at 400°C. The mesophase quality appeared excellent on the hot stage. A standard mesophase evaluation showed that A122 had a domain size of approximately 200µm by visual observation on the annealed sample. Quantitative image analysis was not reliable on this sample because the mesophase in the annealed specimen had so many cracks. The oxygen content of the double-hydrotreated A122 material was still 1.88%, indicating that the O heteroatom structures in these coal extracts are very resistant to removal by hydrogenation. Even with this high oxygen content, the A122 extract still formed a high-quality mesophase.

D. Activation of Coal Extraction Residues

The economics of the coal extraction process would be improved if the extraction residues also had some value. For this purpose, we attempted to activate these materials to produce a high surface area carbon. We obtained samples of the NMP extraction residue of raw coal WVGS-13421, as well as the extraction residue of a coal hydrotreated at 450°C for 2 hours (A-67).

Both materials were activated in a H₂O/N₂ mixture at 900°C using a tumbling furnace. The hydrotreated (A-67) residue was very refractory and after about 81 hours of treatment gave a 64% burn-off. The raw coal residue was much more reactive and gave about 85% burn-off after 48 hours.

The surface areas and pore characteristics were determined for both materials at the Oak Ridge Laboratory by T. Burchell and E. L. Fuller. The measured surface area for the activated residue from the untreated coal was 770 m²/gm while that for the hydrotreated coal was 212 m²/gm. The lower surface area and refractory nature of the hydrotreated residue is expected since it would have a greater ash content than the residue from the untreated coal. Since hydrotreatment increases the extraction yield, it would also lead to a higher ash content in the insoluble residue.

In a subsequent study, we obtained a second sample of the extraction residue from untreated coal and attempted to produce active carbons using different amounts of burn-off. We prepared 3 materials with active carbon yields of 50, 65, and 68%. These samples were also submitted to T. Burchell for surface area measurement. The results are summarized in Table VIII along with our measured ash analysis for these activated carbons. The results show that surface area does increase with increasing burn-off. However, more detailed studies would be needed to determine the optimum activation that can be achieved for these residues.

Table VIII
Active Carbons from Coal Extraction Residue (Activated at 900°C, H₂O)

SAMPLE	ACTIVE CARBON Yd. %	SURFACE AREA m²/gm	% ASH
65-1	50	464	4.6
65-3	65	410	4.3
65-2	68	332	4.2

E. Fabrication of Graphite Artifacts from Hydrotreated Coal Extracts

We produced a graphite artifact using coal extract-derived coke as the filler and the coal extract itself as the binder. The coal extract coke was produced from WVGS-13421 coal hydrotreated for 450°C for 2 hours. The raw coke was prepared at WVU and then calcined to 1,100°C by T. Burchell at the Oak Ridge Laboratory. The same coal NMP extract was used as the binder for graphite fabrication. The extract (D-085) had a 113°C Mettler softening point and a 52.6% MCC value. After milling, the calcined coke was mixed with 1/3 by weight of the coal extract binder and then extruded to produce 19mm-diameter rods. The rods were baked and graphitized to 3,000°C. The properties measured for the graphitized rods were the following:

Coefficient of Thermal Expansion (CTE) = $0.26 \times 10^{-6}/^{\circ}\text{C}$
Specific Resistance = 9.55 micro-ohm-meters
Density = 1.376 g/cc

The very low CTE value of 0.26 is similar to that measured for electrode graphite derived from petroleum needle coke. The relatively low density for the fabricated artifact could be due to an inappropriate binder level or to a puffing effect from the nitrogen in the coke.

V. DISCUSSION

Our screening evaluation studies have demonstrated that the coal extraction process has the potential for producing acceptable products for all the applications anticipated for the program. However, hydrotreatment is necessary to produce materials that are suitable for use as pitches, coke precursors, or mesophase raw materials.

The extract from the hydrotreated coal WVGS-13421, 450° - 2 hours appears to be acceptable as either a carbon binder or impregnation pitch. Summarized in Table IX is a comparison of the properties for the A076 extract with those for commercial coal tar binder and petroleum impregnant pitches. The carbon yield (MCC) for the extract is quite high for a solids-free pitch with a softening point of 105°C. Some of the analytical characteristics of the extract are quite unusual in comparison to those for the commercial pitches. The low aromatic

hydrogen content reflects the effects of hydrotreatment of the precursor coal. The high N and O contents are also unusual for a binder or impregnant pitch material.

Our mesophase evaluation studies show that a material, such as the NMP extract of the WVGS-13421 coal hydrotreated for 450°C for 2 hours, is capable of forming a very large domain mesophase. This extract could therefore be used to produce a mesophase pitch which may be acceptable for fibers. The mesophase quality is comparable to that for precursors of needle coke. The high nitrogen content would be a drawback for processing of such a coke. The excellent mesophase development for a pitch such as the A076 extract is surprising because of its very high oxygen content. A high oxygen content in coal conversion materials has been previously associated with a high reactivity and a poor mesophase quality. Obviously, the form of oxygen in these hydrotreated coal extracts is different from that in typical coal conversion products and does not lead to a fast coking reactivity.

Our results have shown that a hydrotreated coal extract such as the A076 can be used directly as a binder pitch without any subsequent processing. The direct production of pitches by the extraction process could have advantages over the current commercial coal tar binder pitch processes which involve the distillation of coal tar. The need for coke oven processing for tar generation and the handling of by-products from tar distillation would be avoided. It is likely that pitches with different properties could be obtained by controlling the hydrotreatment and extraction conditions.

We have demonstrated that coke derived from hydrotreated coal extract can be used to produce graphite with a low coefficient of thermal expansion, a requisite for graphite electrodes. By altering the processing conditions and the use of blends, it would be possible to produce graphites with varying degrees of anisotropy. We had shown previously that isotropic graphite can be produced from the coal extract⁽¹⁾. No other process has the flexibility for producing this range of carbon materials. The high nitrogen contents of the extracts could, however, be a drawback for the use of these materials for some graphite products.

Finally, the extraction residue can be activated to produce an activated carbon. The best procedure for achieving an optimum active carbon still needs to be defined. However, the use of the residue for a commercial applications would definitely improve total process economics.

Table XI
Properties of Coal Extract and Commercial Pitches

	EXTRACT A076	COAL BINDER	PETROLEUM IMPREGNANT
SP, °C	105	112	120
MCC %	53	58	52
C, %	88.9	93.8	91.5
H, %	5.85	3.92	5.0
N, %	2.20	0.70	0.6
O, %	2.74	0.93	0.5
S, %	0.45	0.56	2.5
ArH %	45	85	55
Mol Wt.	370	410	500

References:

- (1) "Coal-Based Nuclear Graphites for the New Production Gas-Cooled Reactor" DOE Grant DE FG02-91 NP00159, Final Report, May 31, 1994
- (2) R. A. Greinke and L. H. O'Connor, Anal. Chem. 52, 1877 (1980)
- (3) R. T. Lewis, I. C. Lewis, R. A. Greinke, S. L. Strong, Carbon 25, 289 (1987)
- (4) R. T. Lewis, Extended Abstract for 12th Biennial Carbon Conference, Pittsburgh, PA, p. 215, 1975
- (5) E. L. Fuller, ORNL, personal communication

Figures

- Figure 1: Proton NMR in CS₂ Solution for C-269-2, Hydrotreated Coal 450°C - 1 Hour, No Catalyst
- Figure 2: Proton NMR in CS₂ Solution for C-279-1, Hydrotreated Coal 450°C - 1 Hour, Fe₂S₃ Catalyst
- Figure 3: Proton NMR in CS₂ Solution for C-288-2, Hydrotreated Coal 450°C - 1 Hour, Mo(S) Catalyst
- Figure 4: TGA Curve for C-269-2, Hydrotreated Coal 450°C - 1 Hour, No Catalyst
- Figure 5: TGA Curve for C-279-1, Hydrotreated Coal 450°C - 1 Hour, Fe₂S₃ Catalyst
- Figure 6: TGA Curve for C-288-2, Hydrotreated Coal 450°C - 1 Hour, Mo(S) Catalyst
- Figure 7: Gel Permeation Chromatography (GPC) Curve for C-269-2, Hydrotreated Coal 450°C - 1 Hour, No Catalyst
- Figure 8: Gel Permeation Chromatography (GPC) Curve for C-279-1, Hydrotreated Coal 450°C - 1 Hour, Fe₂S₃ Catalyst
- Figure 9: Gel Permeation Chromatography (GPC) Curve for C-288-2, Hydrotreated Coal 450°C - 1 Hour, Mo(S) Catalyst
- Figure 10: Proton NMR in CS₂ for C-300-3, Hydrotreated Coal 450°C - 2 Hours, No Catalyst

- Figure 11: Proton NMR in CS₂ for C-300-6, Hydrotreated Coal 450°C - 2 Hours, Fe₂S₃ Catalyst
- Figure 12: Proton NMR in CS₂ for C-300-9, Hydrotreated Coal 450°C - 2 Hours, Mo(S) Catalyst
- Figure 13: TGA Curve for C-300-3, Hydrotreated Coal 450°C - 2 Hours, No Catalyst
- Figure 14: TGA Curve for C-300-6, Hydrotreated Coal 450°C - 2 Hours, Fe₂S₃ Catalyst
- Figure 15: TGA Curve for C-300-9, Hydrotreated Coal 450°C - 2 Hours, Mo(S) Catalyst
- Figure 16: Gel Permeation Chromatography Curve for C-300-3, Hydrotreated Coal 450°C - 2 Hours, No Catalyst
- Figure 17: Gel Permeation Chromatography Curve for C-300-6, Hydrotreated Coal 450°C - 2 Hours, Fe₂S₃ Catalyst
- Figure 18: Gel Permeation Chromatography Curve for C-300-9, Hydrotreated Coal 450°C - 2 Hours, Mo(S) Catalyst
- Figure 19: Schematic Diagram of Test-Tube Heated Coal Extract
- Figure 20: Proton NMR Spectrum for A076 from Hydrotreated Coal WVGS-13421 - 450°C, 2 Hours
- Figure 21: Proton NMR Spectrum for A066 from Hydrotreated Coal WVGS-13421 - 450°C, 1 Hour
- Figure 22: Proton NMR Spectrum for A073 from Hydrotreated Coal WVGS-13423 - 450°C, 2 Hours
- Figure 23: Proton NMR Spectrum for A075 from Hydrotreated Coal WVGS-13423 - 450°C, 1 Hour
- Figure 24: TGA Curve for A076 from Hydrotreated Coal WVGS-13421 - 450°C, 2 Hours
- Figure 25: TGA Curve for A066 from Hydrotreated Coal WVGS-13421 - 450°C, 1 Hour
- Figure 26: TGA Curve for A073 from Hydrotreated Coal WVGS-13423 - 450°C, 2 Hours
- Figure 27: TGA Curve for A075 from Hydrotreated Coal WVGS-13423 - 450°C, 1 Hour
- Figure 28: Gel Permeation Chromatogram for A076 from Hydrotreated Coal WVGS-13421 - 450°C, 2 Hours

- Figure 29: Gel Permeation Chromatogram for A066 from Hydrotreated Coal WVGS-13421 - 450°C, 1 Hour
- Figure 30: Gel Permeation Chromatogram for A073 from Hydrotreated Coal WVGS-13423 - 450°C, 2 Hours
- Figure 31: Gel Permeation Chromatogram for A075 from Hydrotreated Coal WVGS-13423 - 450°C, 1 Hour
- Figure 32: Proton NMR Spectrum for 250°C Distillation Residue D035-1
- Figure 33: Proton NMR Spectrum for 350°C Distillation Residue D035-2
- Figure 34: Proton NMR Spectrum for 400°C Distillation Residue D035-3
- Figure 35: TGA Curve for 250°C Distillation Residue D035-1
- Figure 36: TGA Curve for 350°C Distillation Residue D035-2
- Figure 37: TGA Curve for 400°C Distillation Residue D035-3
- Figure 38: Annealed Mesophase Pitch from Sample A076
- Figure 39: Annealed Mesophase Pitch from Sample A066
- Figure 40: Annealed Mesophase Pitch from Sample A073
- Figure 41: Annealed Mesophase Pitch from Sample A075
- Figure 42: Area in Annealed Mesophase Pitch from Sample A076
Showing Clusters of Solid Particles

END OF SWEEP

START OF SWEEP

600 PROTON NMR SPECTROSCOPY

37.9 % AROMATIC PROTONS

62.1 % ALIPHATIC PROTONS

2.4% 2% OF THE ALIPHATIC PROTONS

ARE LONG-CHAIN

AROMATIC/ALIPHATIC PROTON RATIO 0.41

N = 30

SIGMA = 25

WILMAD GLASS CO., INC.
U.S. Route 40 and Oak Road
BUENA, N.J. 08310 U.S.A.
MADE IN U.S.A.
W-38-12/77

ppm (delta) 10 9 8 7 6 5 4 3 2 1 0

SWEEP TIME 5 (1) min.

SAMPLE: REMARKS: R. LEWIS/D. RIFKE
Tol-2-1-1 (THERMAL-450) A95-01463
192.1mg

SOLVENT: ULTRASONIC MIXING w/CS2

DEC. LEVEL: CENTRI FUGED

SPECTRUM AMPL. 2000 (80)

FILTER 1 (OPEN) sec

RF POWER 0.05 (0.1) mG

DATE 950510

SPECTRUM NO. 95050808

OPERATOR aff

**Figure 2: Proton NMR in CS₂ Solution for C-279-1, Hydrotreated Coal
450°C - 1 Hour, Fe₂S₃ Catalyst**

Sample: 701-2-1-1 (THERMAL-450) A95-01463
Size: 26.3683 mg
Method: 10C/MIN
Comment: ARGON 100CC/MIN Pt PAN

TGA

File: 95050808A.08
Operator: gfl
Run Date: 18-May-95 16:23

Figure 4: TGA Curve for C-269-2, Hydrotreated Coal 450°C - 1 Hour,
No Catalyst

Sample: 701-2-1-2 (CF1-450)

A95-01464

TGA

File: 95050808B.09

Size: 25.5111 mg

Operator: gfl

Method: 10C/MIN

Run Date: 18-May-95 13:48

Comment: ARGON 100CC/MIN Pt PAN

Figure 5: TGA Curve for C-279-1, Hydrotreated Coal450°C - 1 Hour, Fe₂S₃ Catalyst

Sample: 701-2-1-3 (CF2-450)

A95-01465

TGA

File: 95050808C.05

Size: 24.2128 mg

Operator: gfl

Method: 10C/MIN

Run Date: 12-May-95 15:11

Comment: ARGON 100CC/MIN Pt PAN

Figure 6: TGA Curve for C-288-2, Hydrotreated Coal 450°C - 1 Hour, Mo(S) Catalyst

For Sample: 701-2-1-1

Date Acquired 06/22/95 01:55:58 PM

Project Name: GPC
Sample Name: 701-2-1-1
Vial: 2
Injection: 1
Date Acquired: 06/22/95 01:55:58 PM
Processing Method: GPC
Comments: 95050808-1g3ml TCB Thermal - 450. prepped 5/16/95

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 06/23/95 10:02:42 AM
Pressure: 75
Submitter: hkm

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.617	420	470	456	493	535	1.086609

Figure 7: Gel Permeation Chromatography (GPC) Curve for C-269-2,
Hydrotreated Coal 450°C - 1 Hour, No Catalyst

Project Name:	GPC	Sample Type:	Broad Unknown
Sample Name:	701-2-1-2	Volume:	100.00
Vial:	3	Run Time:	30.0 min
Injection:	1	Date Processed:	06/23/95 10:02:13 AM
Date Acquired:	06/22/95 02:51:24 PM	Pressure:	75
Processing Method:	GPC	Submitter:	hkm
Comments:	95050808 .1g3ml TCB CF-1- 450 prepped 5/16/95

Peak Results

i	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.517	406	479	443	477	512	1.090000

Figure 8: Gel Permeation Chromatography (GPC) Curve for C-279-1, Hydrotreated Coal 450°C - 1 Hour, Fe₂S₃ Catalyst

Project Name: GPC
Sample Name: 701-2-1-3
Vial: 4
Injection: 1
Date Acquired: 06/22/95 03:32:41 PM
Processing Method: GPC
Comments: 95050808 .1g3ml TCB CF-2- 450 prepped 5/16/95

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 06/23/95 10:01:31 AM
Pressure: 75
Submitter: hkm

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.750	372	458	421	465	509	1.129627

Figure 9: Gel Permeation Chromatography (GPC) Curve for C-288-2,
Hydrotreated Coal 450°C - 1 Hour, Mo(S) Catalyst

Figure 11: Proton NMR in CS₂ for C-300-6, Hydrotreated Coal
450°C - 2 Hours, Fe₂S₃ Catalyst

C300-3

Sample: 701-2-16-4

Size: 24.8060 mg

Method: 10C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-01823 TGA

File: 95060801A.01

Operator: gfl

Run Date: 23-Jun-95 11:28

Figure 13: TGA Curve for C-300-3, Hydrotreated Coal
450°C - 2 Hours, No Catalyst

C300-6

Sample: 701-2-16-8

Size: 24.4479 mg

Method: 10C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-01824 TGA

File: 95060801B.01

Operator: gfl

Run Date: 23-Jun-95 08:34

Figure 14: TGA Curve for C-300-6, Hydrotreated Coal
450°C - 2 Hours, Fe₂S₃ Catalyst

C300-9

Sample: 701-2-16-12

Size: 25.1950 mg

Method: 10C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-01825 TGA

File: 95060801C.01

Operator: gfl

Run Date: 22-Jun-95 16:08

Figure 15: TGA Curve for C-300-9, Hydroreated Coal
450°C - 2 Hours, Mo(S) Catalyst

For Sample: 701-2-16-4

Date Acquired 06/16/95 12:43:30 PM

Project Name: GPC
Sample Name: 701-2-16-4
Vial: 2
Injection: 1
Date Acquired: 06/16/95 12:43:30 PM
Processing Method: GPC
Comments: C300-3, Thermal 450-2 prepped 6/15/95 .25g/7ml TCB no fl. rt. mkr. 95060801

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 06/19/95 09:38:03 AM
Pressure: 75
Submitter: RTL

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.817	386	453	421	455	492	1.091709

Figure 16: Gel Permeation Chromatography Curve for C-300-3,
Hydrotreated Coal 450°C - 2 Hours, No Catalyst

Project Name: GPC
Sample Name: 701-2-16-8
Vial: 3
Injection: 1
Date Acquired: 06/16/95 01:23:06 PM
Processing Method: GPC
Comments: C300-6, Fe Cat. 450-2 prepped 6/15/95 .25g/7ml TCB no fl. rt. mkr. 95060801

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 06/19/95 09:37:30 AM
Pressure: 75
Submitter: RTL

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.783	379	455	416	450	483	1.096545

Figure 17: Gel Permeation Chromatography Curve for C-300-6, Hydrotreated Coal 450°C - 2 Hours, Fe₂S₃ Catalyst

Project Name: GPC
Sample Name: 701-2-16-12
Vial: 4
Injection: 1
Date Acquired: 06/16/95 01:55:19 PM
Processing Method: GPC
Comments: C300-9, Mo Cat. 450-2 prepped 6/15/95 .25g/7ml TCB no fl. rt. mkr. 95060801

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 06/19/95 09:36:59 AM
Pressure: 75
Submitter: RTL

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.767	392	457	426	460	498	1.087104

Figure 18: Gel Permeation Chromatography Curve for C-300-9,
Hydrotreated Coal 450°C - 2 Hours, Mo(S) Catalyst

PRODUCTS FROM 400°C-6 HR. HEAT TREATMENTS OF WVU COAL EXTRACTS

(Schematic Diagram)

Figure 19

2000

Figure 21: Proton NMR Spectrum for A066 from Hydrotreated Coal
WVGS-13421 - 450°C, 1 Hour

OPERATOR gff
DATE 951102
SPECTRUM NO. 950

REMARKS: R. L. EWIS
R073 (A95-03027)
CS2
TMS
94% hot CS
SOLUBLE

SAMPLE: _____

SWEPT TIME 5 (1) min.

SOLVENT: _____

SWEPT WIDTH 10 ppm or Hz

END OF SWEEP 0 ppm or Hz

DEC. LEVEL _____

SPECTRUM AMPL. 1500 (50)
 FILTER 1 (OPEN) sec
 RF POWER 0.05 (0.1) mG

WILLYS CORP., INC.
U.S. Route 40 and Oak Road
Beverly Hills, California 90210
Printed in U.S.A.
W-100-11/75

Figure 22: Proton NMR Spectrum for A073 from Hydrotreated Coal
WVGS-13423 - 450°C, 2 Hours

Sample: A076 701-2-30-2

A95-03035 TGA

File: 95090704B.01

Size: 18.5080 mg

Operator: gfl

Method: 10°C/MIN

Run Date: 16-Oct-95 11:52

Comment: ARGON 100CC/MIN Pt PAN

Figure 24: TGA Curve for A076 from Hydrotreated Coal
WGS-13421 - 450°C, 2 Hours

Sample: A066 701-2-30-1

Size: 24.6620 mg

Method: 10°C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-03034 TGA

File: 95090704A.02

Operator: gfl

Run Date: 16-Oct-95 09:35

Figure 25: TGA Curve for A066 from Hydrotreated Coal
WVGS-13421 - 450°C, 1 Hour

TGA V4.0D DuPont 2000

Sample: A073 701-2-30-3

Size: 19.3970 mg

Method: 10°C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-03037 TGA

File: 95090704D.02

Operator: gfl

Run Date: 18-Oct-95 08:49

Figure 26: TGA Curve for A073 from Hydrotreated Coal
WVGS-13423 - 450°C, 2 Hours

Sample: A075 701-2-30-3

Size: 19.0000 mg

Method: 10°C/MIN

Comment: ARGON 100CC/MIN Pt PAN

A95-03036 TGA

File: 95090704C.02

Operator: gfl

Run Date: 17-Oct-95 16:52

Figure 27: TGA Curve for A075 from Hydrotreated Coal
WTGS-13423 - 450°C, 1 Hour

Project Name: GPC

Sample Name: A076

Vial: 4

Injection: 1

Date Acquired: 09/25/95 02:08:13 PM

Processing Method: GPC

Comments: 701-2-30-2(WVU) prepped 7/21/95

Sample Type: Broad Unknown

Volume: 100.00

Run Time: 30.0 min

Date Processed: 09/25/95 03:49:51 PM

Pressure: 73

Submitter: rtl

Peak Results							
#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.850	367	450	408	443	475	1.111614

Figure 28: Gel Permeation Chromatogram for A076 from Hydrotreated Coal
WVGS-13421 - 450°C, 2 Hours

For Sample: A066

Date Acquired 09/25/95 01:11:58 PM

Project Name: GPC
Sample Name: A066
Vial: 3
Injection: 1
Date Acquired: 09/25/95 01:11:58 PM
Processing Method: GPC
Comments: 701-2-30-1(WVU) prepped 7/21/95

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 09/25/95 03:48:09 PM
Pressure: 73
Submitter: rtl

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.717	417	461	449	482	520	1.076375

Figure 29: Gel Permeation Chromatogram for A066 from Hydrotreated Coal
WVGS-13421 - 450°C, 1 Hour

Project Name:	GPC	Sample Type:	Broad Unknown
Sample Name:	A073	Volume:	100.00
Vial:	6	Run Time:	30.0 min
Injection:	1	Date Processed:	09/25/95 03:48:35 PM
Date Acquired:	09/25/95 03:15:40 PM	Pressure:	73
Processing Method:	GPC	Submitter:	rtl
Comments:	701-2-30-4 (WVU) prepped 7/21/95

Peak Results						
#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)
1	15.017	389	436	420	452	488
						Polydispersity
						1.079811

Figure 30: Gel Permeation Chromatogram for A073 from Hydrotreated Coal
WVGS-13423 - 450°C, 2 Hours

Project Name: GPC
Sample Name: A075
Vial: 5
Injection: 1
Date Acquired: 09/25/95 02:44:30 PM
Processing Method: GPC
Comments: 701-2-30-3(WVU) prepped 7/21/95

Sample Type: Broad Unknown
Volume: 100.00
Run Time: 30.0 min
Date Processed: 09/25/95 03:49:10 PM
Pressure: 73
Submitter: rtl

Peak Results

#	Ret Time (min)	Mn (Daltons)	MP (Daltons)	Mw (Daltons)	Mz (Daltons)	Mz+1 (Daltons)	Polydispersity
1	14.800	388	454	429	467	504	1.106079

Figure 31: Gel Permeation Chromatogram for A075 from Hydrotreated Coal
WVGS-13423 - 450°C, 1 Hour

WCV-368-K18-2

W
WILMAD

WILMAD GLASS CO., INC.
U.S. Route 40 and Oak Road
DUENIA, N.J. 08010 U.S.A.

Printed in U.S.A. 10-100-12/79

Sample: D035-1 (701-2-30-5)

A95-02980 TGA

File: A: 95090101A.02

Size: 26.1319 mg

Operator: gfl

Method: 10°C/MIN

Run Date: 6-Sep-95 11:48

Comment: ARGON 100CC/MIN Pt PAN

Figure 35: TGA Curve for 250°C Distillation Residue D035-1

Sample: D035-2 (701-2-30-6)

A95-02981 TGA

File: A: 95090101B.02

Size: 26.2477 mg

Operator: gfl

Method: 10°C/MIN

Run Date: 6-Sep-95 14:12

Comment: ARGON 100CC/MIN Pt PAN

Figure 36: TGA Curve for 350°C Distillation Residue D035-2

Sample: D035-3 (701-2-30-7)

A95-02982

TGA

File: A: 95090101C.01

Size: 25.0206 mg

Operator: gfl

Method: 10°C/MIN

Run Date: 5-Sep-95 12:01

Comment: ARGON 100CC/MIN Pt PAN

Figure 37: TGA Curve for 400°C Distillation Residue D035-3

Figure 38

Annealed Mesophase Pitch from Sample A076

450°C - 2 Hr., Coal WVGS 13421

A076 450 - 2 HR 13421

95091810-2-1 50X PL

500μm

50X, POLARIZED LIGHT

A076

95091810-2-2 250X PL

100μm

250X, POLARIZED LIGHT

Figure 39

Annealed Mesophase Pitch from Sample A066

450°C - 1 Hr., Coal WVGS 13421

50X, POLARIZED LIGHT

250X, POLARIZED LIGHT

Figure 40

Annealed Mesophase Pitch from Sample A073

450°C - 2 Hr., Coal WVGS 13423

A073 450 - 2 Hr 13423

50X PL

95091810-3-1

500 μ m

50X, POLARIZED LIGHT

A073

250X PL

95091810-3-2

100 μ m

250X, POLARIZED LIGHT

Figure 41

Annealed Mesophase Pitch from Sample A075

450°C - 1 Hr., Coal WVGS 13423

A075 450 - 1 HR 13423

50X PL

95091810-4-1

500μm

Figure 42

50X, POLARIZED LIGHT

A075

250X PL

95091810-4-2

100μm

250X, POLARIZED LIGHT

Figure 42

Annealed Mesophase Pitch from Sample A076

450°C - 2 Hr., Coal WVGS 13421

A076

78 X005

4-2-01815056

97 JAN 27 PM 2:52

RECEIVED
JNOE/PETC

500X, BRIGHT FIELD

40μm

A076

78 X005

4-2-01815056

500X, POLARIZED LIGHT (SAME AREA)

FUNCTIONAL MATERIALS DISTRIBUTION

3M COMPANY

Ceramic Materials Department
201-4N-01 3M Center,
St. Paul, MN 55144
M. A. Leitheiser

AIR PRODUCTS AND CHEMICALS

P.O. Box 538
Allentown, PA 18105
S. W. Dean

ALLISON GAS TURBINE DIVISION

P.O. Box 420
Indianapolis, IN 46206-0420
P. Khandelwal (Speed Code W-5)
R. A. Wenglarz (Speed Code W-16)

AMA RESEARCH & DEVELOPMENT CENTER

5950 McIntyre Street
Golden, CO 80403
T. B. Cox

ARGONNE NATIONAL LABORATORY

9700 S. Cass Avenue
Argonne, IL 60439
W. A. Ellingson
J. P. Singh

ARGONNE NATIONAL LABORATORY-WEST

P.O. Box 2528
Idaho Falls, ID 83403-2528
S. P. Henslee

BABCOCK & WILCOX

Domestic Fossil Operations
20 South Van Buren Avenue
Barberton, OH 44023
M. Gold

BRITISH COAL CORPORATION

Coal Technology Development Division
Stoke Orchard, Cheltenham
Gloucestershire, England GL52 4ZG
J. Oakey

CANADA CENTER FOR MINERAL & ENERGY TECHNOLOGY

568 Booth Street
Ottawa, Ontario
Canada K1A 0G1
R. Winston Revic
Mahi Sahoo

DOE

DOE OAK RIDGE OPERATIONS

P.O.Box 2001
Oak Ridge, TN 37831
Assistant Manager for
Energy Research and Development

DOE

DOE OAK RIDGE OPERATIONS

P. O. Box 2008
Building 4500N, MS 6269
Oak Ridge, TN 37831
M. H. Rawlins

DOE

OFFICE OF BASIC ENERGY SCIENCES

Materials Sciences Division
ER-131

19901 Germantown Road
Germantown, MD 20874-1290
H. M. Kerch

DOE

IDAHO OPERATIONS OFFICE

P. O. Box 1625
Idaho Falls, ID 83415
J. B. Malmo

DOE
MORGANTOWN ENERGY TECHNOLOGY
CENTER
P.O. Box 880
Morgantown, WV 26505
R. C. Bedick
D. C. Cicero
F. W. Crouse, Jr.
N. T. Holcombe
W. J. Huber
J. E. Notestein

DOE
OFFICE OF FOSSIL ENERGY
FE-72
19901 Germantown Road
Germantown, MD 20874-1290
J. P. Carr

DOE
OFFICE OF VEHICLE AND ENERGY R&D
CE-151 Forrestal Building
Washington, DC 20585
R. B. Schulz

DOE
OFFICE OF SCIENTIFIC AND TECHNICAL
INFORMATION
P. O. Box 62
Oak Ridge, TN 37831
For distribution by microfiche as shown in
DOE/TIC-4500, Distribution Category:
UC-114 (Coal Based Materials and
Components)

DOE
PITTSBURGH ENERGY TECHNOLOGY
CENTER
P.O. Box 10940
Pittsburgh, PA 15236
A. L. Baldwin
G. V. McGurl
T. M. Torkos

DOW CORNING CORPORATION
3901 S. Saginaw Road
Midland, MI 48686-0995
H. Atwell

EC TECHNOLOGIES
3614 Highpoint Drive
San Antonio, TX 78217
D. J. Kenton

ELECTRIC POWER RESEARCH
INSTITUTE
P.O. Box 10412
3412 Hillview Avenue
Palo Alto, CA 94303
W. T. Bakker
J. Stringer

EUROPEAN COMMUNITIES JOINT
RESEARCH CENTRE
Petten Establishment
P.O. Box 2
1755 ZG Petten
The Netherlands
M. Van de Voorde

GA TECHNOLOGIES. INC.
P.O. Box 85608
San Diego, CA 92138
T. D. Gulden

GAS RESEARCH INSTITUTE
8600 West Bryn Mawr Avenue
Chicago, IL 60631
H. S. Meyer

GEORGIA INSTITUTE OF TECHNOLOGY
Materials Science & Engineering (0245)
Bunger-Henry Building, Room 276
Atlanta, GA 30332-0245
T. L. Starr

IDAHO NATIONAL ENGINEERING
LABORATORY
P. O. Box 1625
Idaho Falls, ID 83415
B. H. Rabin

LAVA CRUCIBLE-REFRACTORIES CO.
P.O. Box 278
Zelienople, PA 16063
T. Mulholland

LAWRENCE LIVERMORE NATIONAL
LABORATORY
P.O. Box 808, L-325
Livermore, CA 94550
W. A. Steele

LOS ALAMOS NATIONAL LABORATORY
P.O. Box 1663
Los Alamos, NM 87545
J. D. Katz

NATIONAL INSTITUTE OF STANDARDS
AND TECHNOLOGY
U.S. Dept. of Commerce
Bldg. 220, Rm A215
Gaithersburg, MD 20899
S. G. Malghan

NATIONAL MATERIALS ADVISORY
BOARD
National Research Council
2101 Constitution Avenue
Washington, DC 20418
K. M. Zwilsky

OAK RIDGE NATIONAL LABORATORY
P.O. Box 2008
Oak Ridge, TN 37831
P. T. Carlson
N. C. Cole
R. R. Judkins
R. A. Lawson (8 copies)
E. L. Long, Jr.
D. P. Stinton
M. R. Upton

OFFICE OF NAVAL RESEARCH
Code 431, 800 N. Quincy Street
Arlington, VA 22217
S. G. Fishman

SANDIA NATIONAL LABORATORIES
Department 6211, MS 0710
Albuquerque, NM 87185
R. J. Buss
G. A. Carlson
A. G. Sault

SHELL DEVELOPMENT COMPANY
P.O. Box 1380
Houston, TX 77251-1380
L. W. R. Dicks

TENNESSEE VALLEY AUTHORITY
Energy Demonstration & Technology
MR2N58A
Chattanooga, TN 37402-2801
C. M. Huang

THE JOHNS HOPKINS UNIVERSITY
Materials Science & Engineering
Maryland Hall
Baltimore, MD 21218
R. E. Green, Jr.

**THE MATERIALS PROPERTIES COUNCIL,
INC.**

United Engineering Center
345 E. Forty-Seventh Street
New York, NY 10017
M. Prager

THE NORTON COMPANY
High Performance Ceramics Division
Goddard Road
Northborough, MA 01532-1545
N. Corbin

THE TORRINGTON COMPANY
Advanced Technology Center
59 Field St.
Torrington, CT 06790
W. J. Chmura

UNION CARBIDE CORPORATION
Linde Division
P.O. Box 44
175 East Park Drive
Tonawanda, NY 14151-0044
Harry Cheung

**UNITED TECHNOLOGIES RESEARCH
CENTER**
MS 24, Silver Lane
East Hartford, CT 06108
K. M. Prewo

UNIVERSITY OF WASHINGTON
Department of Materials Science and
Engineering
101 Wilson, FB-10
Seattle, WA 98195
T. G. Stoebe

**VIRGINIA POLYTECHNIC INSTITUTE &
STATE UNIVERSITY**
Department of Materials Engineering
Blackburg, VA 24601
W. A. Curtin
K. L. Reifsnider

WESTERN RESEARCH INSTITUTE

365 N. 9th Street
P.O. Box 3395
University Station
Laramie, WY 82071
V. K. Sethi

**WESTINGHOUSE ELECTRIC
CORPORATION**
Research and Development Center
1310 Beulah Road
Pittsburgh, PA 15235
S. C. Singhal

DR. CAULTON L. IRWIN
WEST VIRGINIA UNIVERSITY
P. O. BOX 6064
MORGANTOWN, WV 26506-6064

JOHN ZONDLO
WEST VIRGINIA UNIVERSITY
P. O. BOX 6102
MORGANTOWN, WV 26506

AL STILLER
WEST VIRGINIA UNIVERSITY
P. O. BOX 6102
MORGANTOWN, WV 26506

DR. T. D. BURCHELL
OAK RIDGE NATIONAL LABORATORY
P.O. BOX 2008 MS 6088
OAK RIDGE, TN 37831-6088

**PRODUCTION OF ALUMINUM REDUCTION
ELECTRODES FROM SOLVENT-EXTRACTED
COAL-DERIVED CARBON FEEDSTOCKS**

FINAL REPORT

September 20, 1996

**Research sponsored by the U. S. Department of Energy, Fossil
Energy Advanced Research and Technology Development Materials
Program, DOE/FE AA 15 10 10 0, Work Breakdown Structure
Element ALCOA-3**

Report Prepared by
D. L. Belitskus
Aluminum Company of America
Alcoa Technical Center
100 Technical Drive
Alcoa Center, PA 15069-0001
under
Subcontract 86X-SS130C, WBS Element ALCOA-3

for

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831
Managed by
LOCKHEED MARTIN ENERGY RESEARCH CORP.
for the
U. S. DEPARTMENT OF ENERGY
under contract DE-AC05-96OR22464

TABLE OF CONTENTS

Page No.

BACKGROUND	1
<i>Anodes for aluminum production</i>	<i>1</i>
<i>Petroleum coke production</i>	<i>1</i>
<i>Coke evaluations</i>	<i>2</i>
<i>Microstructural analysis</i>	<i>2</i>
<i>Real density and crystallite height</i>	<i>3</i>
<i>Impurities</i>	<i>3</i>
RESULTS FOR TASK 1	3
<i>Real density and crystallite height</i>	<i>6</i>
<i>Chemical analysis</i>	<i>7</i>
<i>Yield on calcination</i>	<i>8</i>
<i>Overall assessment</i>	<i>8</i>
REFERENCES	8

BACKGROUND

Anodes for aluminum production

Anodes for production of aluminum by molten salt electrolysis are commonly manufactured by forming and baking a blend of calcined petroleum coke and coal tar pitch, along with some recycled anode butt material (prebaked anode technology) or by self-baking, in the electrolysis cell, a blend of calcined petroleum coke and coal tar pitch (Soderberg anode technology). Newer cells are of the prebaked anode type. Anode carbon is oxidized to carbon dioxide in the electrochemical reaction, at a theoretical rate of 0.334 kg per kg of aluminum. In practice, consumption rate is higher, generally within the range of 0.400 to 0.500 kg per kg of aluminum, depending on anode type and quality as well as on cell operation. Prebaked anode consumption is usually at the lower end of the range and Soderberg anode consumption at the higher end.

Because anode carbon is consumed as part of the electrochemical reaction during aluminum production, a large quantity of petroleum coke is required for this purpose each year. In recent years, annual calcined petroleum coke usage in the USA for aluminum production anodes has been about 2,000,000 tons and world wide usage has approached 6,000,000 tons.

Petroleum coke production

Petroleum coke, a high carbon content, high molecular weight material that is the major constituent of anodes for electrolytic production of aluminum, is a byproduct from petroleum refineries. The coker receives residual products from a number of refinery operations such as the atmospheric and vacuum distillation and cracking units used to produce higher revenue-generating products such as gasoline, aviation fuel, and lubricants. The coker is operated to maximize the production of "coker gas oil," from which additional products of these kinds are refined.

Not all petroleum coke is suitable for manufacture of anodes for aluminum production. A coke can be unsuitable from a structural standpoint, with too great a porosity to economically produce acceptable anodes. Conversely, it can be too low in porosity, with a "shot" structure that doesn't permit adequate bonding with the coke produced from the binder pitch. Coke can be unsuitable from an impurity standpoint as well. Common impurities in petroleum feedstocks that concentrate in the coke and have undesirable consequences in aluminum production anodes include sulfur, vanadium, and nickel. Currently used refinery feedstocks tend to produce a greater percentage of coke having undesirable physical characteristics and/or impurity levels than feedstocks used in the past.

Because annual aluminum production is increasing while production of high quality petroleum coke is declining, a source of carbon with comparable or improved properties relative to petroleum coke, with the potential for production at a competitive cost, is highly desirable. Coke produced from solvent extracted coal using a process under development in the Chemical Engineering Department at West Virginia University (WVU) has promise for meeting these criteria.

Coke evaluations

Naturally, the most definitive evaluation of a coke for aluminum production anodes is the manufacture and commercial cell testing of full size anodes. This involves many tons of coke, which cannot be supplied with experimental coke production processes.

Aluminum producers have a rather high degree of confidence in the results of certain standardized tests conducted on bench scale anodes, including anode density, permeability, electrical resistivity, air reactivity, carbon dioxide reactivity, and mechanical property tests of several types. However, even this can require an inordinate quantity of experimentally generated coke, typically at least 10 kg.

When even smaller quantities of coke are available, tests only on the cokes themselves must suffice. Although confidence level in the evaluation is lower, this gives a reasonable indication of any major problems with regard to the coke. A complete series of tests can include microstructural examination, chemical analysis, and determinations of real density, crystallite height, grindability, packing density, air and carbon dioxide reactivities, and pore size distribution by mercury porosimetry. The full array of tests requires several kilograms of coke.

For the subcontract reported upon here, a still more preliminary coke screening evaluation was conducted. This consisted of microstructural evaluations and real density and crystallite height determinations. In addition, an impurity assessment was made on a coke produced in an identical manner to one of those tested. Yield after calcination is important from an economic standpoint, and was determined also.

Microstructural analysis

Cokes used in anodes for aluminum production have been well characterized by optical microscopy. A typical coke used for this purpose has a degree of structural ordering that is between that of a highly anisotropic needle coke used in graphite electrode manufacture and that of an isotropic coke.

A particularly useful method of microscopic examination utilizes polarized light with a gypsum phase-sensitive plate. Using this technique, a polished surface of anisotropic carbon appears in the colors yellow, blue, and red, with the colors changing as the specimen is rotated. Needle cokes and, to a lesser extent, cokes used in anodes for aluminum production have distinct areas of ordered structure, with elongated cracks or pores. This is often called a "flow structure." Other cokes have sub-micron areas of ordering (called a "mosaic structure")

and typically little porosity. These cokes are not desirable for anodes for aluminum production. A more extensive discussion of carbon and graphite structural development is given in the section, "Subtask 1.1 Literature Review," in Ref. 1.

Using the method of optical microscopy described above, structural features of new cokes that are candidates for use in anodes for aluminum production can be qualitatively compared with those of cokes that are known to be suitable for this purpose.

Real density and crystallite height

Another useful determination is the coke real density after calcination. Real density refers to the inherent carbon density if pores were eliminated. It is determined by grinding the coke sample to a fine particle size and measuring the density in a medium that can penetrate the majority of the remaining pores. (Kerosene or a similar liquid has been used over the years, but modern helium pycnometers are more convenient and rapid and give comparable results.) Real density indicates the extent of carbon crystallite growth and alignment, which in turn gives an indication of satisfactory reactivity and electrical resistivity. Most commercially calcined petroleum cokes used for aluminum production anodes have a real density between 2.05 and 2.10 g/cc.

Crystallite height (L_c), determined using X-ray diffraction, is an additional indicator of carbon structural ordering. L_c values for calcined petroleum cokes used in anodes for aluminum production usually range from 25 to 35 Å.

Impurities

A preliminary assessment of a potential new coke for aluminum production anodes should include a determination of impurities that are of concern in petroleum cokes. (Although it is possible that impurities in a new coke that are not normally found in petroleum cokes could be a problem, this must be evaluated using the more extensive testing outlined above.)

The work reported upon herein involves Task 1 of the subcontract. Optional Tasks 2 and 3 are contingent upon future funding.

RESULTS FOR TASK 1

1.1 Review reports from WVU on the solvent extraction of coal process, identify materials already produced during the program, and still available, that are most likely to result in a calcined coke having the characteristics necessary for use in aluminum reduction cell anodes, and obtain 250-gram (minimum) quantities of three promising candidates.

Reports from WVU on the United States Department of Energy sponsored project, "Coal Based Nuclear Graphites for the New Production Gas Cooled Reactor," were reviewed, since there is some commonality between cokes for graphite production and cokes for anodes for aluminum production. The final report¹ on Task 1, "Development of Coal-Derived Isotropic

Coke and Nuclear Graphite," was most relevant. Based on the results discussed in that report and in consultation with Dr. Peter Stansberry of WVU, it was decided to test coke produced from an N-methylpyrrolidone (NMP) extract of nonhydrotreated coal WVGS 13423 (Powellton, lower split, Mingo, WV) as well as cokes from the same coal with two conditions of hydrotreatment prior to NMP extraction, 400°C for 1 hr and 450°C for 1 hr. Details of preparation of these types of materials at WVU will not be given here, since the experimental production process has been described in detail in Ref. 1.

Review of the reports also suggested that the calcination process carried out at WVU used both too low a maximum temperature and too slow a heat-up rate to adequately simulate commercial calcination of anode grade coke in a rotary kiln or rotary hearth. Hence, it was planned to establish and verify a bench scale calcination process at Alcoa Technical Center (ATC) to produce calcined coke for this subcontract. To be used in verifying the importance of the calcination procedure, samples of the same three types of cokes calcined at WVU were furnished to ATC along with the uncalcined cokes.

1.2 Contact a calcined petroleum coke supplier and obtain 100-gram (minimum) quantities of a commercially-calcined petroleum coke typically used for aluminum smelting and the corresponding green coke; based on knowledge of important calcination factors, select calcination conditions and calcine the green petroleum coke.

In order to verify the suitability of the laboratory procedure to be used for simulating commercial calcination, samples of ARCO petroleum coke commercially calcined in a rotary hearth at Cherry Point, WA, and the green coke feed to the calciner were obtained from ARCO Products Company (courtesy of Mr. B. C. Vitchus).

Literature on bench scale coke calcination²⁻⁶ was reviewed. Although a variety of specific bench scale procedures have been used, a common theme is that heat-up rate must be very rapid, at least 50°C/min. Also, it has been shown⁷ that commercial calcination corresponds to a 1200° to 1300°C laboratory calcination temperature.

Based on the guidelines outlined above, the following laboratory calcination procedure was adopted. A 90-cm long horizontal tube furnace having an internal diameter of ~10 cm was used. The furnace has three independently controlled heating zones to facilitate temperature control. A 120-cm long, 7.5-cm outer diameter quartz tube was inserted into the furnace cavity. The ends of the tube were fitted with ceramic insulating material. Tubes for inlet and outlet of inert gas penetrated each insulator. In addition, one insulator contained a hole for a pushrod. A quartz boat that could be moved by a steel pushrod having a hooked end was used to contain the coke samples to be calcined. This apparatus is shown schematically in Figure 1.

A 30-g sample of the ARCO green coke was placed in the quartz boat, which in turn was placed within the region of the quartz tube extending outside the furnace. The ends of the quartz tube were stoppered with the ceramic insulators and an argon flow of ~60 L/hr was passed through the tube. Temperature within the portion of the quartz tube located in the

center of the furnace cavity was raised to 1250°C. The boat was pushed into this zone and kept there for 1/2 hr. It was then pulled into the area of the quartz tube extending out of the furnace, allowed to cool under the argon atmosphere, and removed.

1.3 Mount and polish a representative quantity of the commercially calcined petroleum coke and the laboratory calcined petroleum coke, verify from microstructural analysis that the laboratory calcination procedure produced a calcined coke microstructure acceptably similar to the commercially calcined coke sample, and alter conditions and perform a second iteration if required.

A commercial mounting resin was mixed with samples of the laboratory calcined ARCO coke and the commercially calcined coke and these were vacuum cast and cured to produce cylindrical specimens 2.5 cm in diameter by ~2 cm high. One face of each was polished using a polishing wheel and a series of sandpaper discs starting with 120-grit and finishing with 600-grit. Final polish utilized a moleskin disc and 0.3 μm alumina powder. Polished faces were examined microscopically using polarized light and a phase sensitive plate.

Figures 2 and 3 give representative photomicrographs of the two materials. The microstructures are quite comparable. A heat-up rate appreciably slower than that attained in the rotary hearth would have resulted in a much less porous structure. Conversely, if the laboratory heat-up rate had been too rapid, a very high porosity coke could have resulted. Hence, the laboratory calcination process was considered appropriate based on microstructure.

As supporting evidence, real density of the laboratory calcined ARCO coke was determined by helium pycnometer to be 2.08 g/cc. This value is about average for ARCO coke calcined at Cherry Point.

1.4 Calcine the three WVU samples under the conditions selected in Task 1.3; mount and polish the calcined WVU samples and determine whether or not each has a microstructure considered suitable for coke for use in aluminum reduction cell anodes.

The three WVU cokes were calcined according to the procedure described above. The calcined cokes were mounted, polished, and examined microscopically. Many fields of view were examined for each specimen. Although there is naturally some subjectivity in microscopic comparisons, the photomicrograph shown for each material in this report was selected to be representative of the material.

Figure 4 shows the calcined coke from coal that had not been hydrotreated. This coke has a very fine mosaic structure and little porosity. If used in an anode for aluminum production, there would be little opportunity for binder coke to form a good mechanical bond with the coke particles. Hence, coke with this microstructure can be anticipated to form poor anodes for aluminum production. From a macroscopic standpoint, the coke is very "fluffy," probably due to poor packing of the irregularly shaped particles. This would cause problems in material handling and in anode forming.

Figure 5 shows coke from coal that had been hydrotreated at 400°C for 1 hr prior to NMP extraction and Figure 6 shows coke from coal that had been hydrotreated at 450°C for 1 hr. Both of these cokes have an anisotropic microstructure characteristic of petroleum cokes used in anodes for aluminum production. The similarity to the ARCO calcined petroleum coke is obvious by comparing these figures with Figures 2 and 3. There is enough porosity to permit mechanical attachment with binder coke, but not an inordinate amount of porosity that would necessitate excessive binder pitch.

As would be expected from earlier reports from WVU, the higher hydrotreatment temperature resulted in greater anisotropy (a more needle-coke-like microstructure with larger areas of crystallite alignment). This extent of needle-coke-like characteristic would be quite satisfactory for anodes for aluminum production, but it is not believed to be of any real advantage. The ARCO coke appears to have an anisotropy level between those of the two cokes from hydrotreated coal, although this observation is somewhat subjective. Since increasing the extent of hydrogenation increases the cost of the WVU process, coke produced from coal having the 400°C hydrotreatment temperature would be preferred.

Figure 7 shows the microstructure of coke from coal hydrotreated at 450°C for 1 hr and subsequently calcined at WVU to 1100°C using a slow heat-up rate. This coke contains very little porosity, relative to the same coke calcined to 1250°C at a fast heat-up rate (Figure 6). This shows the importance of simulating commercial calcination for evaluating candidate cokes for anodes for aluminum production.

1.5 Determine real density and crystallite height, and estimate impurity levels expected in calcined coke based on WVU analyses of the starting materials and the yields on calcination.

Real density and crystallite height

Real densities of the three WVU cokes calcined at ATC, along with those for the same cokes calcined at WVU, are shown in Figure 8. Real density increased with increasing anisotropy of the coke, i.e. in the order: (1) no coal hydrotreatment, (2) hydrotreatment at 400 °C for 1 hr, and (3) hydrotreatment at 450°C for 1 hr. The values for the ATC-calcined samples from the hydrotreated coal are quite typical of those for petroleum cokes used in anodes for aluminum production and would be expected to result in a reactivity and electrical resistivity comparable to calcined petroleum cokes. The generally lower real densities for the WVU-calcined materials reflect the lower maximum temperature and, perhaps, the slower heat-up rate.

The fact that the ATC-calcined ARCO coke has a real density between those of the two cokes from hydrotreated coal is in qualitative agreement with the indication from the microstructural analyses that the extent of anisotropy of the ARCO coke is between the anisotropies of the two WVU cokes from hydrotreated coal.

Crystallite height values for the three WVU-produced cokes calcined at ATC are 22.4 Å for coke from coal having no hydrotreatment, 28.2 Å for coke from coal hydrotreated at 400°C, and 29.2 Å for coke from coal hydrotreated at 450°C. Like the real densities, these values increase with increasing coke anisotropy. The latter two values are within the range normally found for commercially calcined petroleum cokes.

Chemical analysis

Elemental analysis for a calcined coke that appears to be quite satisfactory for use in anodes for aluminum production (from WVGS 13423 coal that had been hydrotreated at 450°C for 1 hr) was reported upon in Ref. 1. (The analysis is not of the specific production run for the ATC material, but is considered to be adequate for a preliminary assessment of chemical suitability of such a coke.)

Sulfur level in the WVU-produced calcined coke sample is 0.32 wt%, only about one-tenth the sulfur level in a petroleum coke used in aluminum production anodes.⁸ Sulfur serves no useful purpose in an anode, but emits objectionable carbonyl sulfide and sulfur oxides during electrolysis. Hence, the coke produced using the WVU process is extremely good in this regard.

Vanadium and nickel are common impurities found in petroleum coke. They are objectionable from the standpoints of contamination of the aluminum produced as well as being anode air oxidation catalysts. Air oxidation is a contributor to the greater-than-theoretical anode consumption experienced in commercial cells. Typical specifications are 0.045 wt% maximum for vanadium and 0.04 wt% maximum for nickel. Vanadium content in the WVU coke sample analyzed is 0.0002 wt% and nickel content is 0.0038 wt%, far below the specification maximums.

Two other impurities normally monitored in calcined petroleum cokes for use in anodes for aluminum production are iron and silicon. These elements are not found in significant quantities in the petroleum feedstocks to a refinery but rather are reflective of contamination. (Iron can increase from vessel and piping corrosion, silicon can be the result of anti-foaming agents used in the refinery, and any dirt/dust contamination of the calcined coke will result in increases in both elements.) Typical specifications are 0.03 wt% maximum for iron and 0.02 wt% maximum for silicon.

Iron content was 0.065 wt% in the calcined coke sample from WVGS 13423 coal that had been hydrotreated at 450°C for 1 hr. It is likely that some of the iron in this sample is due to contamination during coking and calcining, since it has been found that iron contents of WVU-produced calcined cokes exceed those calculated from iron contents of the precursor extracts, based on volatile matter loss during coking and calcining.¹ Therefore, there is a good possibility that iron content of coke from this process can be reduced to a satisfactory level.

The WVU coke sample that was analyzed is also high in silicon, 0.06 wt%. However, silicon content has varied widely among the calcined cokes made using the WVU process, and this value was the highest for any of the calcined cokes analyzed.¹ Other coals and processing conditions resulted in silicon contents in calcined coke as low as 0.001 wt%. Hence, there is an expectation that a suitable silicon level can be attained.

Yield on calcination

Yield on calcination is not important with regard to the coke itself, but affects the economics of the process. Yields on calcination for the three WVU cokes calcined at ATC were 85.8% for coke from nonhydrotreated coal, 91.4% for coke from coal hydrotreated at 400 °C for 1 hr, and 90.2% for coke from coal hydrotreated at 450 °C for 1 hr. These compare favorably with the yield for the ARCO petroleum coke, 80.7%.

Overall assessment

Two of the three cokes evaluated, those produced from coal that had been hydrotreated, are judged to be quite suitable for use in anodes for aluminum production based on most of these preliminary evaluations. Microstructures, real densities, and crystallite height values are very similar to those for a typical calcined petroleum coke. Levels of several impurities of concern in calcined petroleum cokes (sulfur, nickel, and vanadium) are much lower than those in typical petroleum cokes. The only concerns from these evaluations are high iron and silicon levels, but it seems likely that iron and silicon levels can be reduced. Larger scale testing will ultimately be required to make an unqualified judgment regarding the technical suitability of coke from the WVU process for use in anodes for aluminum production.

The cost of coke from this process is of prime importance if it is to be used in anodes for aluminum production. Cost must be competitive with petroleum coke cost. Although commercial-scale cost for calcined coke by this process has been estimated by the MITRE Corporation to be \$177 per ton⁹, which is competitive with calcined petroleum coke cost, presumably this is for nonhydrotreated coal. Cost would go up with extent of hydrotreatment, so that it is important to minimize such treatment or to otherwise economically provide an anisotropic coke by this process. In the earlier program for producing graphite¹, there was some success in producing anisotropic coke by blending hydrotreated and nonhydrotreated coal prior to NMP extraction. This appears to be one avenue for investigation in future work on coke for anodes for aluminum production.

REFERENCES

1. West Virginia University, "Coal Based Nuclear Graphites for the New Production Gas Cooled Reactor, Task 1: Development of Coal-Derived Isotropic Coke and Nuclear Graphite," (Grant No. DE-FG02-91NP00159), Final Technical Report for the Period March 1, 1991 through February 28, 1994. Submitted to: United States Department of Energy, May 31, 1994.

2. P. J. Rhedey, "Structural Changes in Petroleum Coke During Calcination," Transactions of the Metallurgical Society, vol. 239, pp. 1084-1091, 1967.
3. Anon., "Conoco Test Method for the Laboratory Calcining of Petroleum Coke," Conoco CT-5-80, released for general circulation on April 18, 1983.
4. P. J. Rhedey and S. K. Nadkarni, "Coker Feedstock Characteristics and Calcined Coke Properties," Light Metals 1984, TMS, Warrendale, PA, pp. 859-868, 1984.
5. D. Kocaefe, C. Dubuisson, A. Charette, and L. Castonguay, "Effect of Oxidizing Medium on the Structural Behaviour of Petroleum Coke During Calcination," 21st Biennial Conference on Carbon Extended Abstracts and Program, American Carbon Society, pp. 723-724, 1993.
6. E. A. Heintz, "Effect of Calcination Rate on Petroleum Coke Properties," Carbon, vol. 33, no. 6, pp. 817-820, 1995.
7. D. Belitskus, "Effects of Petroleum Coke Calcination Temperature and Anode Baking Temperature on Anode Properties," Light Metals 1991, TMS, Warrendale, PA, pp. 557-563, 1991.
8. D. Belitskus, "Raw Materials for Anodes and their Effects on Properties," in "Third Australasian Aluminium Smelter Technology Course," The University of New South Wales, Kensington, NSW, Australia, pp. 201-238, 1989.
9. West Virginia University Research Corporation on behalf of West Virginia University, "Production and Screening of Carbon Products Precursors from Coal," (Contract No. DE-AC22-95PC94063) Quarterly Technical Progress Report and Key Personnel Staffing Report Number 5, Reporting Period: January 1, 1996 to March 31, 1996. Submitted to United States Department of Energy, April 1996. (Citing a MITRE Corporation report draft.)

Figure 1. Schematic illustration of the ATC bench scale coke calcination apparatus.

Figure 2. Photomicrograph (200X) of ARCO petroleum coke commercially calcined in a rotary hearth at Cherry Point, WA. Taken using polarized light with a phase-sensitive plate.

Figure 3. Photomicrograph (200X) of ARCO petroleum coke calcined using the ATC bench scale process. Taken using polarized light with a phase-sensitive plate.

Figure 4. Photomicrograph (200X) of coke prepared at WVU (from nonhydrotreated WVGS 13423 coal) and calcined at ATC. Taken using polarized light with a phase-sensitive plate.

Figure 5. Photomicrograph (200X) of coke prepared at WVU (from WVGS 13423 coal that had been hydrotreated at 400°C for 1 hr) and calcined at ATC. Taken using polarized light with a phase-sensitive plate.

Figure 6. Photomicrograph (200X) of coke prepared at WVU (from WVGS 13423 coal that had been hydrotreated at 450°C for 1 hr) and calcined at ATC. Taken using polarized light with a phase-sensitive plate.

Figure 7. Photomicrograph (200X) of coke prepared at WVU (from WVGs 13423 coal that had been hydrotreated at 450°C for 1 hr) and calcined at WVU. Taken using polarized light with a phase-sensitive plate.

Figure 8. Real density values for samples of the three experimental cokes calcined at WVU using a slow heat-up rate and a maximum temperature of 1100°C and samples calcined at ATC using a rapid heat-up rate and a maximum temperature of 1250°C.

DISTRIBUTION LIST

IR PRODUCTS AND CHEMICALS

Attn: S. W. Dean
P. O. Box 538
Allentown, PA 18105

ALCOA TECHNICAL CENTER

Attn: D. L. Belitskus
100 Technical Drive
Alcoa Center, PA 15069-0001

AMA RES & DEV CENTER

Attn: T. B. Cox
5950 McIntyre Street
Golden, CO 80403

MOCO PERFORMANCE PROD. INC.

Attn: G. V. Deshpande
100 McGinnis Ferry Road
Milledgeville, GA 30202-3944

BABCOCK & WILCOX

Domestic Fossil Operations
Attn: M. Gold
20 South Van Buren Avenue
Barberton, OH 44023

BRITISH COAL CORP.

Coal Technology Dev. Div.
Attn: J. Oakey
Stoke Orchard, Cheltenham
Glostershire, England GL52 4ZG

ANADA CENTER FOR MINERAL & ENERGY TECHNOLOGY

Attn: R. Winton Revic, Mahi Sahoo
18 Booth Street
Ottawa, Ontario
Canada K1A 0G1

DEPT. OF ENERGY

DOE Oak Ridge Operations
Attn: Assistant Manager for Energy R&D
P. O. Box 2001
Oak Ridge, TN 37831

DEPT. OF ENERGY

DOE Oak Ridge Operations
Attn: M. H. Rawlins
P. O. Box 2008
Bldg. 4500N, MS 6269
Oak Ridge, TN 37831

DEPT. OF ENERGY

Office of Basic Energy Sciences
Materials Science Division
Attn: H. M. Kerch
R-131, 19901 Germantown Rd
Germantown, MD 20874-1290

DOE MORGANTOWN ENERGY TECH. CTR.

Attn: R.C. Bedick, D.C. Cicero,
F.W. Crouse, Jr, N.T. Holcombe,
W.J. Huber, J.E. Notestein
P. O. Box 880
Morgantown, WV 26505

DEPT. OF ENERGY

OFFICE OF FOSSIL ENERGY FE-72
Attn: J. P. Carr
19901 Germantown Road
Germantown, MD 20874-1290

DOE - Pittsburgh Energy Tech. Ctr.

Attn: A.L. Baldwin, G.V. McGurl,
T.M. Torkos
P. O. Box 10940
Pittsburgh, PA 15236

DOW CORNING CORP.

Attn: H. Atwell
3901 S. Saginaw Road
Midland, MI 48686-0995

EC TECHNOLOGIES

Attn: D. J. Kenton
3614 Highpoint Drive
San Antonio, TX 78217

ELECTRIC POWER RES. INSTITUTE

Attn: W.T. Bakker, J. Stringer
P. O. Box 10412
112 Hillview Avenue
Berkeley, CA 94303

EUROPEAN COMMUNITIES JOINT RESEARCH CENTRE

Petten Establishment
Attn: M. Van de Voorde
P. O. Box 2, 1755 ZG Petten
The Netherlands

FIBER MATERIALS, INC.

Attn: C. Baker
5 Morin Street
Biddeford, ME 04005-4497

DISTRIBUTION LIST

A TECHNOLOGIES INC.
Attn: T. D. Gulden
P.O. Box 85608
San Diego, CA 92138

GAS RESEARCH INSTITUTE
Attn: H.S. Meyer
8600 West Bryn Mawr Avenue
Chicago, IL 60631

GEORGIA INST. OF TECH.
Materials Science & Eng. (0245)
Attn: T. L. Starr
Bunger-Henry Bldg., Room 276
Atlanta, GA 30332-0245

OPPERS INDUSTRIES, INC.
Attn: E. R. McHenry
35 William Pitt Way
Pittsburgh, PA 15238

IDAHO NATIONAL ENGINEERING
LAB
Attn: B. H. Rabin
P.O. Box 1625
Idaho Falls, ID 83415

LAWRENCE LIVERMORE
NATIONAL LAB
Attn: W. A. Steele
P.O. Box 808, L-325
Livermore, CA 94550

NATIONAL MATERIALS ADVISORY
BOARD
National Research Council
Attn: K.M. Zwilsky
11 Constitution Avenue
Washington, DC 20418

OAK RIDGE NATIONAL LAB
Attn: T.D. Burchell, T.P. Carlson,
N.C. Cole, R.R. Judkins,
M.R. Upton, F.D. Johnson (5 XX)
P.O. Box 2008
Oak Ridge, TN 37831

OFFICE OF NAVAL RESEARCH
Attn: S.G. Fishman
Code 431, 800 N Quincy Street
Arlington, VA 22217

INDIA NATIONAL LABORATORIES
Attn: G.A. Carlson
Plot 6211, MS 0710
Albuquerque, NM 87185

SHELL DEVELOPMENT CO.
Attn: L.W.R. Dicks
P.O. Box 1380
Houston, TX 77251-1380

TENNESSEE VALLEY AUTHORITY
Energy Demonstration & Technology
Attn: C.M. Huang
MR2N58A
Chattanooga, TN 37402-2801

3 MATERIALS PROPERTIES
COUNCIL INC.
Advanced Engineering Center
Attn: M. Prager
E. Forty-Seventh Street
New York, NY 10017

THE NORTON COMPANY
High Performance Ceramics Div.
Attn: N. Corbin
Goddard Road
Northborough, MA 01532-1545

THE TORRINGTON COMPANY
Advanced Technology Center
Attn: W.J. Chmura
59 Field Street
Torrington, CT 06790

AR CARBON COMPANY, INC.
Attn: I. Lewis
100 Snow Road
Akron, OH 44130

UNION CARBIDE CORP.
Linde Division
Attn: Harry Cheung
P.O. Box 44, 175 East Park Dr
Tonawanda, NY 14151-0044

UNITED TECHNOLOGIES RES. CTR.
Attn: K.M. Prewo
MS 24, Silver Lane
East Hartford, CT 06108

DISTRIBUTION LIST

UNIVERSITY OF KENTUCKY
Ctr. For Applied Energy Research
Attn: F. Derbyshire
572 Iron Works Pike
Lexington, KY 40511-8433

UNIV. OF WASHINGTON
Dept. of Mats. Sci. & Eng.
Attn: T.G. Stoebe
101 Wilson, FB-10
Seattle, WA 98195

VIRGINIA POLYTECHNIC INST.
& STATE UNIVERSITY
Dept. of Materials Engineering
Attn: W.A. Curtin, K.L. Reifsnider
Blacksburg, VA 24601

WEST VIRGINIA UNIVERSITY
Department of Chemical Engineering
Attn: A.H. Stiller, J.W. Zondlo,
P. G. Stansberry
P. O. Box 6101
Morgantown, WV 26506-6101

WEST VIRGINIA UNIVERSITY
NATIONAL RESEARCH CENTER FOR
COAL & ENERGY
Attn: C. L. Irwin
P. O. Box 6064
Morgantown, WV 26506-6064

CONOCO INC.
K. Tucker
P. O. Box 1267
Ponca City, OK 74602

CONOCO INC.
P. O. Box 2197
Houston, TX 77252-2197
Harlacher

ORNL/Sub/94-SR795/01

FINAL REPORT

**Development Of Carbon-Carbon Composites
From Solvent Extracted Pitch**

June 24, 1996

Research sponsored by the U.S. Department of Energy,
Office of Fossil Energy
Advanced Research and Technology Development Materials Program

Report Prepared by
FIBER MATERIALS, INC.

5 Morin Street
Biddeford, Maine 04005

under
Subcontract 86X-SR795C

for

OAK RIDGE NATIONAL LABORATORY

Oak Ridge, Tennessee 37831
Managed by

: LOCKHEED MARTIN ENERGY RESEARCH CORP.
for the

U.S. DEPARTMENT OF ENERGY
under contract DE-AC05-96OR22464

FMI-PmO-96-R0374

INTRODUCTION

There are several methods used to fabricate carbon-carbon composites. One used extensively in the fabrication of aerospace components such as rocket nozzles and reentry vehicle nosetips, as well as commercial components for furnace fixturing and glass manufacturing, is the densification of a woven preform with molten pitch, and the subsequent conversion of the pitch to graphite through heat treatment. Two types of pitch are used in this process; coal tar pitch and petroleum pitch. The objective of this program was to determine if a pitch produced by the direct extraction of coal could be used as a substitute for these pitches in the fabrication of carbon-carbon composites. The program involved comparing solvent extracted pitch with currently accepted pitches and rigidizing a carbon-carbon preform with solvent extracted pitch for comparison with carbon-carbon fabricated with currently available pitch.

BACKGROUND

Carbon-carbon composites have been manufactured with pitch for over 20 years. From the early 1970's, two pitches have typically been used in this process, Allied Signal's 15V coal tar pitch and Ashland Chemical's A-240 petroleum pitch. Both pitches are the by-product of other processes; coal coking for coal tar pitch and petroleum distillation for petroleum pitch.

The process for fabricating carbon-carbon composites consists of assembling a fiber preform, through consolidation, lay-up, weaving, or some other method, and densifying the preform with pitch. The densification is a series of repetitive process steps, each step consisting of impregnation, carbonization, and graphitization, as depicted in Figure 1.

Figure 1

The number of process cycles depends on required composite density, processing parameters, pitch coking value, etc. The resulting carbon-carbon composite is a very strong, very high temperature material suitable for demanding aerospace and commercial application.

Over the years, several problems have arisen with the use of Allied 15V and Ashland A-240 pitches. Both use the residue of other processes and consistency of such residues cannot be counted on.

There are significant environmental issues, particularly with coal tar pitches. Coking ovens are regularly closed down as the steel industry switches to new methods of steel manufacture, overcoming the significant pollution generated by such ovens. With no coking ovens, there will be no supply of coal tar. Even today, as ovens are closing, new sources of tars must be found which affect the resulting pitch.

As the majority of the petroleum used in the U.S. is imported, the availability of petroleum pitch may not be assured. In addition, the properties of crude oil are changing, often resulting in higher sulfur content and this can significantly affect the properties of petroleum pitch and the resulting carbon-carbon.

What is required is a clean process for making pitch from a very large source of raw material available in the U.S. This will ensure a continuous supply of material

without the worry of environmental issues affecting supply. In addition, if the process is flexible enough, pitches could be manufactured having different properties or, similar pitches could be manufactured from different raw material sources.

West Virginia University has developed a process of extracting the usable hydrocarbon content from coal while leaving the ash behind. This solvent extraction process, using solvent N-methyl pyrrolidine (NMP), has shown that pitches suitable for making coke for smelting electrodes can be produced. It has also been shown that the properties of the pitch can be varied so that the resulting coke can range from isotropic on one end of a scale to anisotropic on the other, depending on the degree of hydrogenation applied to the coal before extraction. Being able to vary the properties of the pitch can have several advantages:

- Adjust the process so different raw coals can produce equivalent pitch products.
- Adjust the process so one coal can produce a variety of pitches useful in many applications.
- Tailor a pitch to have specific properties.

For the past eight years, workers in the Chemical Engineering Department at West Virginia University have been developing a technique based on solvent extraction of coal whereby significant quantities of the organic material in coal can be separated from the inorganic contaminants^(1,2,3,4). This process employs a novel class of organic compounds known as dipolar aprotic solvents. When bituminous coal is treated with these solvents at their normal boiling point, much of the carbonaceous material in the coal is solubilized and the inorganic matter remains as an undissolved solid. Through simple filtration the solution is separated from the residual inorganic solids and the organic material is reconstituted by solvent evaporation. Through efficient use of

evaporative technologies, virtually all of the solvent is recovered and recycled in the process. A typical concentration of inorganic matter in the extracted product (as measured by ASTM ashing techniques) is as low as 0.1%. Depending on the starting coal, significant reduction in sulfur species can also be achieved. It has been found that extract yields in the range of 30 to 50% by weight of the original coal can be realized for most bituminous coals indigenous to the Appalachian region. Moreover, if the raw coal is first treated by mild hydrogenation, extract yields as high as 80% can be achieved. Most importantly, by adjusting processing conditions and/or blending extracts from the hydrogenated and raw coals together, desirable properties of the product can be enhanced. It has been shown that the solvent extract can serve as an excellent precursor for a wide range of carbon product feedstocks. Indeed, a successful program has just been completed for the U.S. Department of Energy in which cokes produced from the solvent extraction process were utilized as feedstocks for the production of fine-grained, isotropic graphite⁽⁵⁾. The current program was able to draw from WVU's success to date in the fabrication of carbon-carbon composites.

Evaluation Procedure

To determine whether a solvent extracted pitch is capable of producing carbon-carbon composites having properties similar to currently produced composites, it is necessary to determine if the pitch properties are similar to properties of pitches currently in use. This was accomplished by testing a pitch produced by the Chemical Engineering Department of West Virginia University processed by the solvent extraction process, and comparing it to other pitches. The WVU pitch was processed from WVGS 13421 coal by first hydrogenating the ground in a proton donor, tetralin, at 450°C for 2 hours. This was followed by extraction with n-methyl pyrrolidine (NMP), after which the solution is filtered and the NMP removed by rotary evaporation. A second extraction was carried out using toluene to remove toluene insolubles, thus reducing the softening point. The resulting pitch was identified as WVU D026 pitch.

For this program, a 500 gram sample of WVU D026 pitch was tested with samples of Ashland A-240 and Allied 15V pitches. The test matrix presented in Table 1 was used for these evaluations.

TABLE 1
Pitch Test Matrix

PROPERTY	TEST PROCEDURE
Coking Value	ASTM D-2416
Ash Content	ASTM D-2415
Quinoline Insoluble	ASTM D-2318
Toluene Insoluble	ASTM D-4072
Sulfur	ASTM D-1552
Softening Point	ASTM D-36
Specific Gravity	ASTM D-71

Samples of WVU, Ashland, and Allied pitches were also coked so the grain structure could be evaluated. The coked samples were impregnated with epoxy resin and polished to a metallographically smooth surface, the final polishing done with 0.05 μ alumina powder slurry. Samples of each were then observed under a light microscope using polarized light, with significant observations documented with photomicrographs. Polarized light allows the qualitative analysis of the anisotropy of the pitches.

The next step was to compare how the WVU pitch would impregnate a carbon fiber preform as the first step toward fully processing a carbon-carbon composite. It typically takes four or five cycles of impregnation, carbonization, and graphitization to densify a carbon-carbon billet. As this requires considerable pitch, on the order of a minimum of 25 to 30 kilograms, only one cycle could be completed in this program. Once pilot plant quantities of WVU pitch can be produced, the densification can be completed.

The usual process for impregnating a preform involves melting the pitch in one container by heating. In a second container, connected to the first by a tube and valve, the preform is heated to the same temperature as the pitch. A vacuum is pulled on the vessel holding the preform to remove all gas. When the valve between the two vessels is opened, the molten pitch flows from the container holding the pitch under atmospheric pressure into the evacuated container holding the preform. A considerable amount of extra pitch is required to ensure the transfer vacuum is not lost by air entering the transfer tube from the pitch melter.

Because the quantity of available WVU pitch was minimal, a different technique was utilized. Preforms measuring 13 cm by 13 cm by 5 cm were placed in containers. Each preform was covered with 4.5 kilograms of pitch, one with WVU pitch, the other with Allied 15V pitch. The WVU pitch consisted of two lots, 1 kg of D054 and 3.5 kg of D087. Both lots were manufactured using the same process used for the previously tested lot D026. The two containers were placed in an impregnator which was sealed and evacuated. The impregnator was heated to 250°C under vacuum and held for 4 hours. The vessel was then backfilled with nitrogen to atmospheric pressure, forcing the molten pitch into the preform, filling the voids. Although not as efficient as the hot pitch transfer method described earlier, this method works well with small parts and limited quantities of pitch. The impregnator was allowed to cool and the two cans removed for further processing.

The cans were next placed in a carbonization oven and heated to approximately 800°C under a nitrogen blank at heating rates of approximately 20°C per hour from ambient to 350°C, 5°C per hour from 350° to 600°C per hour, and 10°C per hour from 600°C to 800°C. This process slowly converts the organic pitch to carbon, driving off nitrogen, oxygen, hydrogen, sulfur, and other elements which make up the organic pitch. The resulting carbon, or coke, is amorphous in nature with almost no crystallinity.

Once the pitch has been coked, the rigidized preform is removed from its container and excess coke removed, in preparation for converting the amorphous coke to crystalline graphite. This is accomplished by heating the part to 2525°C, again under a nitrogen blanket to prevent oxidation. This heat treatment takes about 30 hours to accomplish, followed by a 1/2 hour hold prior to cooldown.

Upon completion of rigidization, the carbon-carbon parts were machined to remove excess coke. The parts were then measured and weighed for density determination. Samples extracted from each billet were mounted in epoxy, polished metallographically, and observed under a light microscope to compare the microstructures of the WVU and Allied pitches in the carbon-carbon composite.

RESULTS

Evaluation of the WVU pitch resulted in the properties shown in Table 2.

TABLE 2
WVU Solvent Extracted Pitch Lot D026

PROPERTY	VALUE
Coking Value - %	49.3
Ash Content - %	0.02
Quinoline Insoluble - %	0.39
Toluene Insoluble - %	1.12
Sulfur - %	0.4
Softening Point - °C	117
Specific Gravity	1.22

A comparison was made of this data to a data base of pitch properties established over the last 20 years for Allied 15V pitch and Ashland A-240 pitch. This comparison is shown in Table 3.

TABLE 3
Comparison Of Pitch Analyses

PROPERTY	WVU D026	ASHLAND A-240	ALLIED 15V
Number Of Lots	1	14	30
Coking Value - %	49.3	50.2	46.7
Ash Content - %	0.02	0.03	0.17
Quinoline Insoluble - %	0.39	0.15	4.3
Toluene Insoluble - %	1.12	6.52	14.8
Sulfur - %	0.4	2.0	0.54
Softening Point - °C	117	117	88
Specific Gravity	1.22	1.26	1.28
Viscosity - Sec	--	16	19

It can be seen that the WVU pitch compares very favorably to both Ashland A-240 petroleum pitch and Allied 15V coal tar pitch. With the exception of sulfur, and toluene insoluble contents, D026 is nearly identical to the Ashland pitch. The lower toluene insoluble content is due to the toluene extraction carried out in the pitch manufacturing process to reduce the softening point to an acceptable value. The lower sulfur is also a reflection of the solvent extraction process, as well as the low sulfur coal used as a raw material. In addition to the toluene insoluble content, the 15V pitch also exhibits higher quinoline insoluble content and a lower softening point.

Coked samples of the three pitches were observed under a light microscope to qualitatively evaluate the isotropy/anisotropy of the pitch. Two types of crystal structure

were observed for each material, a finer grain structure and a coarser grain structure. These are shown in Figures 2 and 3 respectively. Figure 2 is the finer grain structure. It can be seen that the Allied 15V pitch has the finest grain structure of the three. This is due to the higher quinoline insoluble fraction acting as nucleation sites in the pitch. The Ashland A-240 and WVU D026 pitches have lower quinoline insoluble, so do not have the nucleation sites available for the fine grain crystallization. The grain size of the Ashland and WVU pitches compare very favorably.

In Figure 3, areas of each sample having larger grains were observed. Again the grains of the Ashland and WVU pitches compare very well. Although the grains in the 15V pitch do not appear as free flowing as the other two materials, the observed grain size compares favorably.

The key observation is that all three pitches produce essentially on anisotropic coke. The coal tar pitch may have localized area of isotropy due to local pockets high in insoluble matter acting as nucleation sites, but in general the structure of this material is also anisotropic.

During the rigidization of a carbon fiber preform, the density was measured after each step in the process. The results are shown in Table 4.

TABLE 4
In Process Composite Densities

PROCESS STEP	ALLIED 15V MATRIX	WVU PITCH MATRIX
Preform	0.75	0.75
After Carbonization	1.07	1.04
After Graphitization	1.07	1.06
After Machining	1.11	1.07
Density Increase	0.36	0.32

COKES FROM SOLVENT EXTRACTED, COAL TAR, AND PETROLEUM PITCHES

Figure 2a: WVU D026 HiPIC Coke

Figure 2b: Ashland A240 HiPIC Coke

Figure 2c: Allied 15V HiPIC Coke

COKES FROM SOLVENT EXTRACTED, COAL TAR, AND PETROLEUM PITCHES

Figure 3a: WVU D026 HiPIC Coke

Figure 3b: Ashland A240 HiPIC Coke

Figure 3c: Allied 15V HiPIC Coke

Samples from each carbon-carbon composite were mounted in epoxy and polished for observation under a light microscope. Significant observations are shown in the photomicrographs in Figures 4 and 5. Figure 4 compares the microstructure of a matrix pocket in the woven structure of fibers. The WVU solvent extracted pitch appears more anisotropic than the coal tar pitch, as was seen in the coked pitch samples discussed earlier. The difference in isotropy is not so great so as to be of concern. Variations of this magnitude are seen throughout normal carbon-carbon processing.

Figure 5 compares fiber bundles which have been impregnated with the two pitches. It can be seen that both pitches impregnate the fiber bundles well, and become well crystallized. The photomicrographs are taken under polarized light, with the matrix showing considerable optical activity, as did the matrix materials in the pockets between fibers.

DISCUSSION

The results of the WVU pitch analysis and comparison to pitches currently used in the fabrication of carbon-carbon composites indicate that the WVU solvent extraction process can produce a pitch which is similar to currently used pitches. Not only are the physical properties of the pitches similar, the microstructure of coked samples of the pitches are also similar. Another criteria of how similar the WVU pitch is, is to compare it to other pitch specifications.

Allied 15V pitch and Ashland A-240 pitch are made to specifications peculiar to each. Although different, there are many similarities, as shown in Table 5.

CARBON-CARBON COMPOSITE MATRIX POCKET

Figure 4a: WVU D026 Pitch Impregnated C/C

Figure 4b: Allied 15V Pitch Impregnated C/C

CARBON-CARBON COMPOSITE FIBER BUNDLE

Figure 5a: WVU D026 Pitch Impregnated C/C

Figure 5b: Allied 15V Pitch Impregnated C/C

TABLE 5
Pitch Specifications

PROPERTY	ALLIED 15V SPECIFICATION	ASHLAND A-240 SPECIFICATIONS	WVU D026 ACTUAL
Coking Value - %, min	35	40	49.3
Ash Content - %, max	0.25	0.15	0.02
Quinoline Insoluble - %, max	6	1	0.4
Toluene Insoluble - %, max	22	10	1.1
Sulfur - %, max	0.7	3	0.4
Softening Point - °C	95 max	130	117
Specific Gravity	1.24-1.32	1.20-1.30	1.22
Viscosity - Sec, max	23	--	--

It is readily evident that WVU pitch D026 meets all the requirements of the Ashland A-240 specification. In addition, it meets all the requirements of the Allied 15V specification with the exception of the softening point and specific gravity. One would therefore conclude that using the WVU pitch in a carbon-carbon composite should result in a composite similar to composites currently being manufactured.

To demonstrate this, two carbon fiber preforms were rigidized, one using Allied 15V pitch, the other with WVU solvent extracted pitch. A comparison of the density increase between the two parts, 0.36 g/cc for the 15V part and 0.32 g/cc for the WVU pitch part, show that, in fact, the WVU pitch should yield carbon-carbon composites have properties similar to composites currently being fabricated with Allied and Ashland pitches.

The minor density difference between parts may be attributed to the density difference in the pitch itself, or may be an artifact of processing. Continued processing

through four or five subsequent densification cycles would aid in clarifying this, as well as provide composite material for preliminary mechanical and thermal property testing. Unfortunately, follow-on programs are not currently planned to either produce additional pitch, nor perform additional processing, even though the work performed to present is very promising.

The photomicrographs taken of the two carbon-carbon composites further confirm their similarity. Both samples show well impregnated fiber bundles, important for the mechanical properties of the composite. Impregnation of the matrix pockets was equivalent for both materials. Some pockets showed more pitch than others in both samples. This is due to the fact that the preform had only undergone one densification cycle. Further densification cycles will result in all the matrix pockets being equally densified. Pitch typically fills the pocket from the walls inward, which was observed in the samples evaluated. The photomicrographs shown in Figure 4 are at the bottom of a pocket, near the fiber bundle, so a large area of matrix is visible. Again the matrix in both materials is observed to be very similar, although the WVU pitch is somewhat more anisotropic than the Allied 15V coal tar pitch. However, this was to be expected from the observations of the coked pitches conducted earlier in the program.

Having worked with one WVU pitch in pitch analysis and carbon-carbon processing, it is believed this material shows great promise in providing a long term, stable, cost effective supply of pitch for producing carbon-carbon composites. It has also led to a number of recommendations for continued work in this area.

First, and foremost, is the need to complete the densification of the carbon-carbon composites which are currently rigidized so preliminary mechanical properties can be determined for a more thorough evaluation of the pitch's ability. This will provide the basis for a more in-depth material characterization program to establish a data base of information.

Second, further work needs to be done to modify the properties of WVU pitch, and then evaluate how these changes will affect carbon-carbon properties. One change would be to increase the density and lower the softening point so a WVU pitch will meet the Allied 15V pitch specification. Another change would be to develop a pitch with a higher density and higher coking value. Increasing the density to 1.5 g/cc and the coking value to 80% will reduce the number of process cycles required for a carbon-carbon composite to reach a density of 1.9 g/cc from five to two. This would reduce carbon-carbon costs on the order of 50% or greater, making it more cost competitive in high temperature applications.

A-third area of further research is the development of a higher strength, high strain carbon foam from the WVU pitch. This foam can then be used as a very low cost preform, replacing the costly woven fiber preform, in a carbon-carbon composite. This type of carbon-carbon processing is promising in the mass production market for such products as pistons in internal combustion engines or low cost tactical missile nozzles.

As more is learned about these solvent extracted pitches, new applications will be developed. The clean process has alleviated environmental concerns of both coal tar and petroleum pitch processes. The huge supply of domestic coal assures a ready domestic supply of these pitches. The economics of the process ensure the pitches will be cost competitive with current pitches. The ease of varying pitch properties will allow the production of a variety of pitches for a variety of composite materials. These parameters will lead to robust carbon-carbon manufacturing once the needed research is concluded.

REFERENCES

- 1) Renganathan, K., Zondlo, J.W., Mintz, E.A., Kneisl, P., Stiller, A.H.; Fuel Proc. Tech., 18, p. 273 (1988).
- 2) Zondlo, J.W., Stiller, A.H.; Preparation of an Ultra Low Ash Coal Extract Under Mild Conditions, Proceedings Conf. Coal-Derived Materials & Chemicals, May 2-3, 1991, Morgantown, WV.
- 3) Stiller, A.H., Zondlo, J.W.; Carbon Products from Coal, Tech for Competitive Growth in West Virginia, October 28, 1992, Shephard College, WV.
- 4) Maslyk, M.L., Zondlo, J.W., Stansberry, P.; Physical and Optical Characterization of West Virginia Coal - Derived Cokes and Graphites, Senior Project, ChE-197, December, 1993.
- 5) Coal Based Nuclear Graphites For The New Production Gas Cooled Reactor, Final Report, DoE Grant DE-FG02-91-NP00159, May 1994.

FUNCTIONAL MATERIALS DISTRIBUTION

3M COMPANY
Ceramic Materials Department
201-4N-01 3M Center,
St. Paul, MN 55144
M. A. Leitheiser

AIR PRODUCTS AND CHEMICALS
P.O. Box 538
Allentown, PA 18105
S. W. Dean

ALCOA ALUMINUM COMPANY
100 Technical Drive
Alcoa Center, PA 15069-0001
D. Belitskus

ALLISON GAS TURBINE DIVISION
P.O. Box 420
Indianapolis, IN 46206-0420
P. Khandelwal (Speed Code W-5)
R. A. Wenglarz (Speed Code W-16)

AMA RESEARCH & DEVELOPMENT CENTER
5950 McIntyre Street
Golden, CO 80403
T. B. Cox

AMOCO PERFORMANCE PRODUCTS, INC.
4500 McGinnis Ferry Road
Alpharetta, GA 30202-3944
G. V. Deshpande

ARGONNE NATIONAL LABORATORY
9700 S. Cass Avenue
Argonne, IL 60439
W. A. Ellingson

BABCOCK & WILCOX
Domestic Fossil Operations
20 South Van Buren Avenue
Barberton, OH 44023
M. Gold

BRITISH COAL CORPORATION
Coal Technology Development Division
Stoke Orchard, Cheltenham
Gloucestershire, England GL52 4ZG
J. Oakey

CANADA CENTER FOR MINERAL & ENERGY
TECHNOLOGY
568 Booth Street
Ottawa, Ontario
Canada K1A 0G1
R. Winston Revic
Mahi Sahoo

DOE
DOE OAK RIDGE OPERATIONS
P.O.Box 2001
Oak Ridge, TN 37831
Assistant Manager for
Energy Research and Development

DOE
DOE OAK RIDGE OPERATIONS
P. O. Box 2008
Building 4500N, MS 6269
Oak Ridge, TN 37831
M. H. Rawlins

DOE
OFFICE OF BASIC ENERGY SCIENCES
Materials Sciences Division
ER-131
19901 Germantown Road
Germantown, MD 20874-1290
H. M. Kerch

DOE
IDAHO OPERATIONS OFFICE
P. O. Box 1625
Idaho Falls, ID 83415
J. B. Malm

DOE
MORGANTOWN ENERGY TECHNOLOGY
CENTER
P.O. Box 880
Morgantown, WV 26505
R. C. Bedick
D. C. Cicero
F. W. Crouse, Jr.
N. T. Holcombe
W. J. Huber
J. E. Notestein

DOE
OFFICE OF FOSSIL ENERGY
FE-72
19901 Germantown Road
Germantown, MD 20874-1290
J. P. Carr

DOE
OFFICE OF VEHICLE AND ENERGY R&D
CE-151 Forrestal Building
Washington, DC 20585
R. B. Schulz

DOE
OFFICE OF SCIENTIFIC AND TECHNICAL
INFORMATION
P. O. Box 62
Oak Ridge, TN 37831
For distribution by microfiche as shown in
DOE/TIC-4500, Distribution Category:
UC-114 (Coal Based Materials and
Components)

DOE
PITTSBURGH ENERGY TECHNOLOGY
CENTER
P.O. Box 10940
Pittsburgh, PA 15236
A. L. Baldwin
G. V. McGurl
T. M. Torkos

DOW CORNING CORPORATION
3901 S. Saginaw Road
Midland, MI 48686-0995
H. Atwell

EC TECHNOLOGIES
3614 Highpoint Drive
San Antonio, TX 78217
D. J. Kenton

ELECTRIC POWER RESEARCH INSTITUTE
P.O. Box 10412
3412 Hillview Avenue
Palo Alto, CA 94303
W. T. Bakker
J. Stringer

EUROPEAN COMMUNITIES JOINT
RESEARCH CENTRE
Petten Establishment
P.O. Box 2
1755 ZG Petten
The Netherlands
M. Van de Voorde

FIBER MATERIALS, INC.
5 Morin Street
Biddeford, ME 04005-4497
C. Baker

GA TECHNOLOGIES, INC.
P.O. Box 85608
San Diego, CA 92138
T. D. Gulden

GAS RESEARCH INSTITUTE
8600 West Bryn Mawr Avenue
Chicago, IL 60631
H. S. Meyer

GEORGIA INSTITUTE OF TECHNOLOGY
Materials Science & Engineering (0245)
Bunger-Henry Building, Room 276
Atlanta, GA 30332-0245
T. L. Starr

KOPPERS INDUSTRIES, INC.
1005 William Pitt Way
Pittsburgh, PA 15238
E. R. McHenry

IDAHO NATIONAL ENGINEERING
LABORATORY
P. O. Box 1625
Idaho Falls, ID 83415
B. H. Rabin

LAWRENCE LIVERMORE NATIONAL
LABORATORY
P.O. Box 808, L-325
Livermore, CA 94550
W. A. Steele

LOS ALAMOS NATIONAL LABORATORY
P.O. Box 1663
Los Alamos, NM 87545
J. D. Katz

NATIONAL MATERIALS ADVISORY BOARD
National Research Council
2101 Constitution Avenue
Washington, DC 20418
K. M. Zwilsky

OAK RIDGE NATIONAL LABORATORY
P.O. Box 2008
Oak Ridge, TN 37831
T. D. Burchell
P. T. Carlson
N. C. Cole
R. R. Judkins
R. A. Lawson (8 copies)
M. R. Upton

OFFICE OF NAVAL RESEARCH
Code 431, 800 N. Quincy Street
Arlington, VA 22217
S. G. Fishman

SANDIA NATIONAL LABORATORIES
Department 6211, MS 0710
Albuquerque, NM 87185
G. A. Carlson

SHELL DEVELOPMENT COMPANY
P.O. Box 1380
Houston, TX 77251-1380
L. W. R. Dicks

TENNESSEE VALLEY AUTHORITY
Energy Demonstration & Technology
MR2N58A
Chattanooga, TN 37402-2801
C. M. Huang

THE MATERIALS PROPERTIES COUNCIL,
INC.
United Engineering Center
345 E. Forty-Seventh Street
New York, NY 10017
M. Prager

THE NORTON COMPANY
High Performance Ceramics Division
Goddard Road
Northborough, MA 01532-1545
N. Corbin

THE TORRINGTON COMPANY
Advanced Technology Center
59 Field St.
Torrington, CT 06790
W. J. Chmura

UCAR CARBON COMPANY, INC.
12900 Snow Road
Parma, OH 44130
I. Lewis

UNION CARBIDE CORPORATION
Linde Division
P.O. Box 44
175 East Park Drive
Tonawanda, NY 14151-0044
Harry Cheung

UNITED TECHNOLOGIES RESEARCH
CENTER
MS 24, Silver Lane
East Hartford, CT 06108
K. M. Prewé

UNIVERSITY OF KENTUCKY
Center for Applied Energy Research
3572 Iron Works Pike
Lexington, KY 40511-8433
F. Derbyshire

UNIVERSITY OF WASHINGTON
Department of Materials Science and
Engineering
101 Wilson, FB-10
Seattle, WA 98195
T. G. Stoebe

VIRGINIA POLYTECHNIC INSTITUTE &
STATE UNIVERSITY
Department of Materials Engineering
Blacksburg, VA 24601
W. A. Curtin
K. L. Reifsnider

WESTERN RESEARCH INSTITUTE
365 N. 9th Street
P.O. Box 3395
University Station
Laramie, WY 82071
V. K. Sethi

WESTINGHOUSE ELECTRIC CORPORATION
Research and Development Center
1310 Beulah Road
Pittsburgh, PA 15235
S. C. Singhal

**EVALUATION OF PITCHES AND COKES
FROM SOLVENT-EXTRACTED
COAL MATERIALS**

FINAL REPORT

August 7, 1995 To August 6, 1996

Report Prepared by
E. R. McHenry
Koppers Industries Inc.
Harmarville Technical Center
1005 Wm. Pitt Way
Pittsburgh, PA 15238
under
Subcontract 86X-SS131V, WBS Element Koppers - 3
for

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831
Managed by
LOCKHEED MARTIN ENERGY RESEARCH CORP.
For the
U. S. DEPARTMENT OF ENERGY
under contract DE-AC05-96OR22464

I. SUMMARY

Three initial coal-extracted (C-E) samples were received from the West Virginia University (WVU) Chemical Engineering Department. Two samples had been hydrogenated to obtain pitches that satisfy rheological requirements. One of the hydrogenated (HC-E) samples had been extracted by toluene to remove ash and higher molecular weight aromatic compounds.

We were unable to measure the softening point and viscosity of the non-hydro treated solid extract sample. Positive characteristics in the HC-E materials were softening points of 113-119°C, low sulfur and ash. The oxygen and nitrogen content of the HC-E samples may limit future usage in premium carbon and graphite products. Coking values were similar to petroleum pitches.

Laboratory anode testing indicates that in combination with standard coal-tar pitch, the HC-E material can be used as a binder pitch.

II. INTRODUCTION

The closure of by-product coal coking oven batteries has resulted in up to a 3% per annum reduction in domestic coal-tar production during the middle of the 1990's. This source reduction has affected industrial capability to produce quantities of quality of binder and impregnating pitches used in the aluminum and commercial carbon and graphite industries. The objectives of this research are to develop dependable domestic coal-based raw materials for the production of: binder pitches for aluminum cell anodes and commercial carbon and graphite products; impregnating pitches for commercial carbon and graphite products and specialty materials; oils for wood treatment and carbon black production; and metallurgical and foundry grade cokes.

We reviewed the processing and product properties of the coal extract materials prepared by WVU. The WVU coal extraction process coupled with hydrogenation yields materials that have potential binder and impregnation application.

We performed standard characterization of small-scale extracts. This information was shared with our Carbon Products Consortium (CPC) partners (Alcoa, Amoco, Conoco, FMI, UCAR and WVU). We also formed small carbon artifacts to demonstrate the binding capability of the laboratory-extracted pitches.

Our studies are summarized in the following sections of this report.

III. EXPERIMENTAL PROCEDURES

- A. Pitch property measurement methods as measured by Koppers are listed in Table I.

Table I
Methods for Measuring Pitch Properties

Characterization	Unit	Method
Softening Point (sp)	°C	ASTM D 3104 (Mettler)
Viscosity	cP	ASTM D 5018
Toluene Insoluble (TI)	wt. %	ASTM D 4072
Quinoline Insoluble (QI)	wt. %	ASTM D 2318 or D 4746
β-Resin (β-R)	wt. %	TI - QI
Modified Conradson Carbon Coking Value (MCC)	wt. %	ASTM D 2416
Density, 25°C	g/cm ³	ASTM D 71 (Water) or D 4892 (Helium)
Ash	wt. %	ASTM D 2415
Carbon and Hydrogen	wt. %	LECO CHN Analyzer
Elemental Analysis	ppm	Atomic Absorbtion (ASTM Draft Method)
Sulfur	wt. %	LECO Sulfur Analyzer
Thermogravimetric Analysis (TGA)		UCAR, using TA Instruments Model 951 Module (10°C/min. in inert atmosphere)

B. Bench-Scale Anode Production

1. Raw Materials

- Sized petroleum coke provided by a commercial aluminum smelter.
- Experimental and commercial pitches.

2. Mix Design as Provided by a Commercial Smelter.

3. Forming Conditions (50 mm-diameter mold)

- 185°C mixing temperature
- 105°C molding
- 7500 psi molding pressure

4. 1150°C Maximum Baking Temperature

- 10°C/Hr 0-600°C
- 25°C/Hr 600-1150°C
- 13-Hour hold at 1150°C

(Inert gas purge throughout baking and cooling cycle.)

C. Anode Testing

Carbon anode testing methods at Koppers are detailed and supported by established quality control procedures. Koppers is directly involved in establishing carbon testing methods in ASTM and ISO; consequently, these methods or methods-under-development are used wherever possible. Statistical process control is used at each test station. A list of our typical testing methods with units is summarized in Table II.

Table II
Carbon Anode Property Measurements

Characterization	Unit
Apparent Density	g/cm ³
Electrical Resistivity	μΩm
Air Permeability	nPm
Compressive Strength	Mpa
Coefficient of Thermal Expansion to 300°C	10 ⁻⁶ /°C
Thermal Conductivity	W/m-°K

IV. EXPERIMENTAL RESULTS

A. Initial WVU Coal Extract Sample Study

Three initial coal-extracted samples were received from WVU. The first extract sample was hydro-treated to form Sample No. 2. Sample No. 3 represents the toluene-extract from Sample No. 2. Our analyses are summarized in Table III.

Table III**Analyses of Three Coal Extract Samples from WVU**

Sample No.	1	2	3
	Solvent Extracted Residue from Coal	Hydrogenated Sample 1	Toluene-Extracted Material from Sample 2
SP, °C	Not Analyzed	119.2	112.8
TI, wt.%	92.7	11.5	1.3
QI, wt.%	2.4	0.5	0.02
β -R, wt.%	90.3	11.0	1.28
Density (25°C) g/cm ³	1.272	1.206	1.217
Ash, wt.%	.25	0.07	0.0
MCC, wt.%	NA	50.7	44.8
C/H, wt.%	1.35	1.31	1.23
C, wt.%	89.97	89.57	88.84
H, wt.%	5.88	5.72	6.04
N, wt.%	2.09	2.04	1.72
O, wt.%	1.32	2.06	2.67
S, wt.%	0.74	0.37	0.42
Viscosity, cps:			
@150°C	Not Analyzed	12,160	2395
@160°C	Not Analyzed	2,430	909
@180°C	Not Analyzed	430	209
@200°C	Not Analyzed	150	72

Sample Nos. 2 and 3 have softening points and viscosities that will enable use as binders or impregnants. The sulfur, ash and QI are sufficiently low for use as an impregnant. The coking value reflects the low QI levels and aromaticity. The oxygen and nitrogen levels are higher than desirable; however, these levels are lower than in most mild gasification pitch type materials.

The TGA data in Figures 1 and 2 were measured by our CPC partner, UCAR. These results are similar to earlier samples produced at WVU for a UCAR study.¹ This illustrates repeatable bench-scale production at WVU.

B. Bench-Scale Anode Study

Because we only had about 500 grams each of the HC-E pitches, it was decided to perform a limited bench-scale anode forming study. We used 110°C sp coal-tar pitch (P-1) and petroleum pitch (P-2) as controls. The primary trial pitch was the No. 2 HC-E 119°C sp sample and was labeled P-3.

In order to explore an alternate approach of the trial material, a 20% HC-E P-3 pitch blend was made with the standard coal-tar pitch. The analyses of the control and trial binder pitches are compared in Table IV. With the 20/80 P-4 blend we have achieved typical binder pitch properties.

Following the guidelines outlined in the Experimental Procedure Section, 50 mm diameter x ~120 mm anodes were formed with the four pitches. Because this was new molding equipment, optimum binder levels were unknown. The trial pitch quantities only permitted the forming of a single anode at each different binder level. Two anodes were formed at each binder level for the control pitches.

The baked carbon test data are summarized in Table V and Figures 3-9. The optimum binder may have been obtained for the petroleum pitch via the 15-16% range; however, the other three pitches require more anode forming at higher percentage levels. The baked density and other properties show that more work is required to complete this study. The property trends provide encouragement for additional larger-scale anode evaluations.

¹I. C. Lewis, R. T. Lewis and H. K. Mayer, "Coal Precursors for Production of Carbon and Graphite Products - Final Report" Subcontract 62X-SR928C, WBS Element - UCAR-3, April 8, 1996.

Sample: R95-1498 (D057-2)

A96-00891 TGA

File: C: 96030401A.03

Size: 25.3470 mg

Operator: gfl

Method: 10C/MIN

Run Date: 5-Mar-96 12:56

Comment: ARGON 100CC/MIN Pt PAN TGA #5904

Sample: R95-1499 (D057-3)

A96-00892 TGA

File: C: 96030401B.02

Size: 25.1250 mg

Operator: gfl

Method: 10C/MIN

Run Date: 5-Mar-96 08:27

Comment: ARGON 100CC/MIN Pt PAN TGA #5904

Table IV

Analyses of Pitches Evaluated in 50 mm
Diameter Molded Anodes

Number	P-1	P-2	P-3	P-4
Type	Coal Tar Standard	Petroleum Standard	Hydrogenated Coal-Extract	20% P-3 80% P-1
SP, °C	111.6	112.0	119.2	114.5
TI, wt. %	30.3	3.2	11.5	26.5
QI, wt. %	14.7	0.1	0.5	11.9
β -R, wt. %	15.6	3.1	11.0	14.6
MCC, wt. %	57.8	46.9	50.7	57.3
Density, g/cm ³	1.33	1.22	1.21	1.31
Ash, wt. %	0.24	0.03	0.07	0.20

Table V

Control and Trial Pitch Baked Anode Characterization

Sample No.*	Core GAD (g/cc)	Core Baked Apparent Density (g/cc)	E.R. ($\mu\Omega\text{m}$)	Air Perm. (nPm)	Crush Strength (Mpa)	CTE Avg. Alpha (E-6/ $^{\circ}\text{C}$ @ 300 $^{\circ}\text{C}$)	Thermal Conductivity (W/m- $^{\circ}\text{K}$)	In-Situ Coking Value (wt. %)
P-1-13	1.556	1.501	97.9	4.82	16.44	3.996	1.86	63.1
P-1-14	1.626	1.553	67.1	1.09	33.59	3.655	2.27	57.5
P-1-15	1.613	1.538	74.2	2.22	26.31	3.976	2.20	61.8
P-1-16	1.633	1.561	65.7	1.56	34.40	3.877	2.23	62.6
P-1-17	1.659	1.571	61.7	0.55	40.92	3.865	2.37	62.4
P-2-13	1.603	1.511	77.6	1.65	22.83	3.845	2.23	50.6
P-2-14	1.621	1.527	71.0	1.45	26.32	3.830	2.15	51.9
P-2-15	1.643	1.540	65.7	0.89	28.87	3.816	2.33	53.6
P-2-16	1.648	1.535	62.5	1.31	28.89	3.738	2.29	52.7
P-3-14	1.553	1.480	89.3	8.38	12.94	3.616	2.02	59.9
P-3-15	1.581	1.498	85.2	9.05	14.22	3.938	1.96	57.2
P-4-15	1.588	1.502	82.3	4.82	18.49	3.926	2.03	60.1
P-4-16	1.625	1.538	69.6	1.31	27.69	4.189	2.25	60.7

*Sample No. shows the pitch type and the binder level in percent. The two control pitch sample Nos. (P-1 and P-2) are the average of two 50 mm diameter anodes. The trial pitch samples (P-3 and P-4) are single anodes.

V. CONCLUSIONS

- The HC-E pitches have softening points and viscosities that will enable application as binders or impregnants. The low insolubles assure impregnating capability.
- An increase in coking value and a decrease in oxygen and nitrogen contents in the HC-E pitches are required for binder and impregnant applications.
- Because of insufficient sample, only two binder levels (14 and 15%) were investigated for the HC-E experimental pitch in the bench-scale anodes; consequently, the optimum anode binder level could not be determined. Nonetheless, preliminary results are promising.
- - The quantity of 20% of HC-E pitch blended with 80% of standard coal tar pitch also only permitted two binder levels (15 and 16%); again, the optimum binder level was not obtained. The performance of the blend pitch is projected to be almost as good as 100% coal tar pitch.

VI. RECOMMENDATIONS FOR FUTURE WORK

- Obtain sufficient quantities of HC-E samples to enable the forming of vibrated 4-inch diameter anodes at a minimum of six binder levels.
- Larger samples will also allow preparation of several blends of HC-E pitch and coal-tar pitch for optimization study.
- Extract hydro treatment optimization as related to anode properties should be studied.
- The initial evaluation of extract and HC-E materials as feedstocks for other binders, oils and cokes should be performed.

E. R. McHenry

FIGURE 3
GREEN APPARENT DENSITY

FIGURE 4
BAKED APPARENT DENSITY

FIGURE 5
ELECTRICAL RESISTIVITY

FIGURE 6
AIR PERMEABILITY

FIGURE 7
COMPRESSIVE STRENGTH

FIGURE 8

COEFFICIENT OF THERMAL EXPANSION

FIGURE 9
THERMAL CONDUCTIVITY

DISTRIBUTION LIST

AIR PRODUCTS AND CHEMICALS
Attn: S. W. Dean
P.O. Box 538
Allentown, PA 18105

ALCOA TECHNICAL CENTER
Attn: D. L. Belitskus
100 Technical Drive
Alcoa Center, PA 15069-0001

AMA RES & DEV CENTER
Attn: T. B. Cox
5950 McIntyre Street
Golden, CO 80403

AMOCO PERFORMANCE PROD. INC.
Attn: G. V. Deshpande
4500 McGinnis Ferry Road
Alpharetta, GA 30202-3944

BABCOCK & WILCOX
Domestic Fossil Operations
Attn: M. Gold
20 South Van Buren Avenue
Barberton, OH 44023

BRITISH COAL CORP.
Coal Technology Dev. Div.
Attn: J. Oakey
Stoke Orchard, Cheltenham
Gloucestershire, England GL52 4ZG

CANADA CENTER FOR MINERAL
& ENERGY TECHNOLOGY
Attn: R. Winton Revic, Mahi Sahoo
568 Booth Street
Ottawa, Ontario
Canada K1A 0G1

DEPT. OF ENERGY
DOE Oak Ridge Operations
Attn: Assistant Manager for Energy R&D
P. O. Box 2001
Oak Ridge, TN 37831

DEPT. OF ENERGY
DOE Oak Ridge Operations
Attn: M. H. Rawlins
P. O. Box 2008
Bldg. 4500N, MS 6269
Oak Ridge, TN 37831

DEPT. OF ENERGY
Office of Basic Energy Sciences
Materials Science Division
Attn: H. M. Kerch
ER-131, 19901 Germantown Rd
Germantown, MD 20874-1290

DOE MORGANTOWN ENERGY
TECH. CTR.
Attn: R.C. Bedick, D.C. Cicero,
F.W. Crouse, Jr, N.T. Holcombe,
W.J. Huber, J.E. Notestein
P. O. Box 880
Morgantown, WV 26505

DEPT. OF ENERGY
OFFICE OF FOSSIL ENERGY FE-72
Attn: J. P. Carr
19901 Germantown Road
Germantown, MD 20874-1290

DOE - Pittsburgh Energy Tech. Ctr.
Attn: A.L. Baldwin, G.V. McGurl,
T.M. Torkos
P.O. Box 10940
Pittsburgh, PA 15236

DOW CORNING CORP.
Attn: H. Atwell
3901 S. Saginaw Road
Midland, MI 48686-0995

EC TECHNOLOGIES
Attn: D. J. Kenton
3614 Highpoint Drive
San Antonio, TX 78217

ELECTRIC POWER RES. INSTITUTE
Attn: W.T. Bakker, J. Stringer
P.O. Box 10412
3412 Hillview Avenue
Palo Alto, CA 94303

EUROPEAN COMMUNITIES
JOINT RESEARCH CENTRE
Petten Establishment
Attn: M. Van de Voorde
P. O. Box 2, 1755 ZG Petten
The Netherlands

FIBER MATERIALS, INC.
Attn: C. Baker
5 Morin Street
Biddeford, ME 04005-4497

DISTRIBUTION LIST

GA TECHNOLOGIES INC.
Attn: T. D. Gulden
P. O. Box 85608
San Diego, CA 92138

GAS RESEARCH INSTITUTE
Attn: H.S. Meyer
8600 West Bryn Mawr Avenue
Chicago, IL 60631

GEORGIA INST. OF TECH.
Materials Science & Eng. (0245)
Attn: T. L. Starr
Bunger-Henry Bldg., Room 276
Atlanta, GA 30332-0245

KOPPERS INDUSTRIES, INC.
Attn: E. R. McHenry
1005 William Pitt Way
Pittsburgh, PA 15238

IDAHO NATIONAL ENGINEERING
LAB
Attn: B. H. Rabin
P. O. Box 1625
Idaho Falls, ID 83415

LAWRENCE LIVERMORE
NATIONAL LAB
Attn: W. A. Steele
P. O. Box 808, L-325
Livermore, CA 94550

NATIONAL MATERIALS ADVISORY
BOARD
National Research Council
Attn: K.M. Zwilsky
2101 Constitution Avenue
Washington, DC 20418

OAK RIDGE NATIONAL LAB
Attn: T.D. Burchell, T.P. Carlson,
N.C. Cole, R.R. Judkins,
M.R. Upton, F.D. Johnson (5 XX)
P.O. Box 2008
Oak Ridge, TN 37831

OFFICE OF NAVAL RESEARCH
Attn: S.G. Fishman
Code 431, 800 N Quincy Street
Arlington, VA 22217

SANDIA NATIONAL LABORATORIES
Attn: G.A. Carlson
Dept. 6211, MS 0710
Albuquerque, NM 87185

SHELL DEVELOPMENT CO.
Attn: L.W.R. Dicks
P. O. Box 1380
Houston, TX 77251-1380

TENNESSEE VALLEY AUTHORITY
Energy Demonstration & Technology
Attn: C.M. Huang
MR2N58A
Chattanooga, TN 37402-2801

THE MATERIALS PROPERTIES
COUNCIL INC.
United Engineering Center
Attn: M. Prager
345 E. Forty-Seventh Street
New York, NY 10017

THE NORTON COMPANY
High Performance Ceramics Div.
Attn: N. Corbin
Goddard Road
Northborough, MA 01532-1545

THE TORRINGTON COMPANY
Advanced Technology Center
Attn: W.J. Chmura
59 Field Street
Torrington, CT 06790

UCAR CARBON COMPANY, INC.
Attn: I. Lewis
12900 Snow Road
Parma, OH 44130

UNION CARBIDE CORP.
Linde Division
Attn: Harry Cheung
P.O. Box 44, 175 East Park Dr
Tonawanda, NY 14151-0044

UNITED TECHNOLOGIES RES. CTR
Attn: K.M. Prewo
MS 24, Silver Lane
East Hartford, CT 06108

DISTRIBUTION LIST

UNIVERSITY OF KENTUCKY
Ctr. For Applied Energy Research
Attn: F. Derbyshire
3572 Iron Works Pike
Lexington, KY 40511-8433

UNIV. OF WASHINGTON
Dept. of Mats. Sci. & Eng.
Attn: T.G. Stoebe
101 Wilson, FB-10
Seattle, WA 98195

VIRGINIA POLYTECHNIC INST.
& STATE UNIVERSITY
Dept. of Materials Engineering
Attn: W.A. Curtin, K.L. Reifsnider
Blacksburg, VA 24601

WEST VIRGINIA UNIVERSITY
Department of Chemical Engineering
Attn: A.H. Stiller, J.W. Zondlo,
P. G. Stansberry
P. O. Box 6101
Morgantown, WV 26506-6101

WEST VIRGINIA UNIVERSITY
NATIONAL RESEARCH CENTER FOR
COAL & ENERGY
Attn: C. L. Irwin
P. O. Box 6064
Morgantown, WV 26506-6064

CONOCO INC.
K. Tucker
P. O. Box 1267
Ponca City, OK 74602

CONOCO INC.
P. O. Box 2197
Houston, TX 77252-2197
G. Harlacher