Reduced size of ordered moments of a quasi 1d antiferromagnet Sr_2CuO_3

K.Kojima^a, M.Larkin^a, G.M.Luke^a, B.Nachumi^a, Y.J.Uemura^a, H.Eisaki^b, M.Motoyama^b, S.Uchida^b, B.J.Sternlieb^c, G.Shirane^c

^a Department of Physics, Columbia University,
538W 120th. st., New York, NY 10027, USA

^b Department of Applied Physics, University of Tokyo,
Hongo 7-3-1, Tokyo 113, JAPAN

^c Brookhaven National Laboratory,
Upton, New York 11973-5000, USA

RECEIVED
SEP 19 1986
OSTI

The quasi one-dimensional antiferromagnet Sr_2CuO_3 exhibits Néel order of Cu^{2+} moments ($S=1/2$) at $T_N = 5.41(1)$ K, as demonstrated by (1) almost resolution-limited magnetic Bragg reflections in neutron scattering measurements, and (2) spontaneous muon spin precession in zero-field muon spin relaxation (μSR) measurements. The temperature dependence of the order parameters are consistent between the two experimental techniques. From the neutron data, we obtained an upper-limit for the ordered moment size of $\sim 0.06 \mu_B$. This indicates a significant moment reduction from quantum fluctuations. *

1. INTRODUCTION

One-dimensional spin systems with antiferromagnetic interactions have been investigated eagerly, because of pronounced quantum mechanical effects reflecting the low-dimensionality. For example, the 1d Heisenberg model with antiferromagnetic interactions takes a singlet ground state, regardless of the spin value of the localized moments. For the half odd-integer cases, the excitation spectrum is gapless and the correlation function shows a power-law decay [1, 2]. These features indicate the 'almost-Néel-ordered' ground-state of half-odd integer spin-chain. Hence, with finite couplings between the chains, half-odd-integer spin-chains are expected to show a Néel order, which has been observed in $S=1/2$ quasi one-dimensional antiferromagnets, such as KCuF_3 ($T_N = 39\text{K}$), $\text{CuCl}_2 \cdot \text{NC}_3\text{H}_5$ ($T_N = 1.7\text{K}$) and Sr_2CuO_3 ($T_N = 5.5\text{K}$). Intuitively, the ratio of the Néel temperature to the intra-chain coupling (T_N/J) is a parameter to measure the extent to which a material is one-dimensional. So far, the antiferromagnet Sr_2CuO_3 has the smallest such ratio ($T_N/J \sim 5.5/1307 \sim 0.004$) [3, 4], suggesting that this compound is the best one-dimensional spin system currently available. We have investigated the magnetic ordered state of this material with muon

spin relaxation (μSR) and elastic neutron scattering measurements.

2. RESULTS

Single crystal Sr_2CuO_3 ($\sim \phi 3\text{mm} \times 2\text{cm}$) was grown at Department of Applied Physics, University of Tokyo, employing the traveling-solvent-floating-zone (TSFZ) method. The crystal structure of

Figure 1:

The crystal structure of Sr_2CuO_3 . The Cu-O antiferromagnetic spin-chain runs in the b -axis direction.

Sr_2CuO_3 is shown in Fig.1. Chains of corner sharing

* This research has been financially supported by NEDO and Packard fellowship. One of the authors (K.K) is supported by JSPS.

MASTER

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**