LA-SUB--94-121

FINAL REPORT

Originating Super-Strong Liquid Crystalline Polymers (SSLCPs)

(9-XA0-H7428-1 Subcontract at UNC)

Executive Summary sentence: Work at UNC focused on a detailed analyses of local chain motion in SSLCPs (aromatic ring mobility in polyamides) via quantitative measurements and simulations of deuterium NMR spectra of labelled polymers prepared at LANL.

Summary Statement of Work: The work at UNC Chapel Hill focused on the experimental characterization of ring mobility in labelled polyaramides with deuterium Nuclear Magnetic Resonance (NMR). Los Alamos National Laboratory prepared the deuterium-labelled analogs of Super-Strong (SS) LCPs and oligomers. These materials were studied to ascertain the influence of substituent size (at the diacid moiety) on the mobility of the labelled diamine. The results are currently being finalized for publication in a refereed journal (*Macromolecules*); an abbreviated account has appeared in *Polymer Preprints* 34, 716 (1993).

Summay of research at UNC: The primary goal of the UNC effort was the development of characterization techniques for SSLCP materials. In particular, we wanted to extend deuterium NMR (DMR) to specific SSLCPs in an effort to understand the role of substituents on local mobility. The longer range goal was to ultimately demonstrate correlations between bulk properties and microscopic mobility and order. We are found evidence from the DMR lineshape of labelled Kevlar-like SSLCPs that adding substituents on the diacid inhibits diamine ring motion in the backbone of these Kevlar-like polymers. We were also able to investigate the influence of chain linearity on local ring motions in this class of polymers, contrasting *meta*-substitution with *para*-substitution and an intermediate degree of nonlinearity using 2,5-substituted thiophene diacid monomer.

We anticipated that such NMR characterization studies of the Kevlar-like SSLCPs might yield correlations between the reported physical properties of a high performance polymer (Kevlar) and local monomer behavior, as one begins to perturb the Kevlar structure with sidechains. The role of sidechain size on local mobility could impact synthetic design efforts to tailor bulk properties of new (SSLCPs) as well as conventional high performance polymers.

Summary of PPTA Studies: Poly(p-phenyleneterephthalamide) (PPTA or Kevlar) is one of the most widely used high performance polymers because its extended-chain

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

morphology in the solid state provides a material with outstanding strength-to-weight properties.¹ The extended-chain morphology of PPTA derives from chain parallelism in its liquid crystalline phase—concentrated solutions of PPTA in H_2SO_4 —which, in turn, comes about because of the rectilinear secondary structure of the polymer chain.² In this paper, the dynamics of the phenyl ring in the solid state of a number of modified aromatic polyamides (modifications of the terephthalic acid monomer via changing the linearity of the backbone and varying the size of substituents on the terephthalic acid monomer) were studied by solid state ^2H NMR to ultimately understand structure-property relationships.

Experimental Details

PPTA was prepared by copolymerizing p-phenylene diamine and terephthalic acid by using Higashi's phosphorylation reaction³. Similar procedure was used to prepare poly(p-phenyleneisophthalamide) and poly(p-phenylene-2,5-thiophene diamide).⁴ PPTA derivatives were made by replacing the terephthalic acid with 2-bromo-terephthalic acid, 2-nitro-terephthalic acid, 2-phenyl-terephthalic acid, 2-(4-benzamido-phenoxy) terephthalic acid, 2-benzamido-terephthalic acid, and 2-dibenzamido-terephthalic acid (Table 1). The polymerization of p-phenylene diamine with 2-benzamido-terephthalic acid and 2-dibenzamido-terephthalic acid was accompanied by an intramolecular cyclization reaction and that chemistry is discussed in a separate paper⁵. In all the polymers under study here, the phenyl ring in the diamine was perdeuterated. In some cases, phenyl ring other than the diamine ring was perdeuterated for comparison.

Solid state ^2H NMR experiments were performed on a Bruker MSL360 spectrometer operating at a deuterium resonance frequency of 55.284 MHz. Spectra were acquired with either a standard quadrupolar echo sequence ($\pi/2 - \tau - \pi/2 - t_2 - \text{Acquire}$)⁶ or a composite-pulse quadrupolar echo sequence ($[\underline{120}, \underline{168}, \underline{80}, \underline{126}] - \tau - [\underline{120}, \underline{168}, \underline{80}, \underline{126}] - t_2 - \text{Acquire}$)⁷. The flip angle of each element in the composite pulse is shown in degrees and an overbar indicates a 180° phase shift. The $\pi/2$ pulse was 2.0 - 2.4 μs in length which was sufficiently short to allow spectral acquisition with minimal spectral distortion. In both sequences, the delay time τ was 20 μs and the recycle delay was set to 30 seconds. The time delay t_2 was set to a value so that acquisition started before the echo top. Acquired data were shifted to locate the top of the echo prior to Fourier transformation. There are not any significant difference between lineshapes observed with these two pulse sequences.

Table 1. Structures of PPTA and its derivatives under study.

Principal Findings

The ²H lineshapes for all the PPTA derivatives under studied shows some general features: the lineshape appears to be a composite of static Pake powder pattern ($\eta = 0$) and one characteristic of rapid 180° ring flips ($\eta = 0.6$). The fraction of rings undergoing 180° ring flips can be estimated qualitatively by comparing experimental lineshapes with lineshape simulations assuming a bimodal distribution of correlation times: $\tau_c > 0.1$ s for the static component and $\tau_c < 1 \times 10^{-9}$ s for the mobile component. In all cases, spectra taken at 360K show a higher percentage of mobile component than spectra taken at 300K (Figure 1). It should be emphasized that the focus here is on qualitative comparisons among the PPTA derivatives. Elaborate computer simulations have further delineated the librational motions of the PPTA polymer chain in earlier reports by English et al.⁸⁻¹⁰

Two different molecular weight PPTA's ($[\eta] = 1.50$ dL/g, see Figure 1 and $[\eta] = 7.61$ dL/g) with the diamine ring labelled show similar ring mobility. Free volume associated with chain ends is therefore not a major factor on the ring mobility. Also, the mobility of the terephthalate ring and the diamine ring was shown to be similar.

Figure 1. Solid state ^2H NMR of PPTA with perdeuterated diamine ring ($[\eta] = 1.50\text{dL/g}$) at 300K and 360K.

The linearity of the PPTA backbone was changed by replacing the terephthalate ring with the isophthalate ring and the 2,5-thiopheneacrylate to alter the rectilinear conformation of the polymer backbone. The fraction of mobile diamine rings in all three cases show only subtle differences. While the nonlinearity of the polymer backbone does not seem to affect the conjugation of the amide group with the phenyl ring, there is some evidence that it restricts the mobility of the diamine ring.

For the substituted (bromo, nitro, phenyl, 2-(4-benzamido-phenoxy)) PPTAs, the fraction of mobile diamine rings is higher than in the unsubstituted PPTA. It has been shown that phenyl substituted PPTA has a high solubility in both dimethylacetamide (DMAc) and N-methyl-2-pyrrolidone (NMP) due to the bulkiness and the degree of rotational freedom of the phenyl substituent.^{11,12} This lateral ring forces the adjacent carbonyl out of the plane of the ring and, therefore, decreases the conjugation within the terephthalate ring. As a result, the diamine ring in phenyl substituted PPTA shows high mobility. For the bromo, nitro, 2-(4-benzamido-phenoxy)) substituted PPTAs, it is interesting to note that they have high diamine ring mobility as in the case of phenyl. The bulkiness of the lateral group seems to be a major factor to affect the conjugation of the amide group with the diamine ring while the size of the lateral group does not show significant influence on the ring mobility.

For the benzoamido substituted PPTAs, the diamine ring mobility is severely retarded. This observation can be rationalized by recognizing the steric interactions between the diamine ring and the phenyl ring of the side chain brought about by intramolecular ring closure. In order to further understand the role of steric interactions on ring dynamics, the repeat unit of this polymer was evaluated in the MMX calculation using PCMODEL (Serena Software). It turns out that the diamine ring has very high rotational energy barrier while the phenyl ring of the side chain has a very negligible rotational energy barrier. Solid state ^2H NMR of the polymer having a perdeuterated phenyl ring in the side chain confirms the differential mobilities for the two rings in the polymer.

Conclusions

The deuterium NMR characterization of the Kevlar-like SSLCPs at UNC are dramatic and expected to yield correlations between the reported physical properties of a high performance polymer (Kevlar) and local monomer behavior, as one begins to perturb the Kevlar structure with sidechains. We are in the process of publishing the study about the role of sidechain size on local mobility via deuterium NMR. We are also carrying out detailed spectral simulations in order to extract the rates of local mobility as a function of temperature and substituent size. Such information will direct synthetic design efforts to tailor bulk properties of new (SSLCs) and conventional high performance polymers.

References:

1. Du Pont Data Manual for Kevlar Aramid, 1986.
2. Yang, H.H., in "Aromatic High Strength Fibers", Wiley, New York, 1989, Chap.2.
3. Higashi, F., Ogata, S., and Aoki, A., J. Polym. Sci. Polym. Chem. Ed., 1982, 20, 2081.
4. Stompel, S., DeSimone, J.M., Samulski, E.T., and J. Preston, Polym. Prepr., 1992, 33, 1194.
5. Benicewicz, B. C., Doak, R. A., and Dec, S. F., Polym. Prepr., in press.
6. Davis, J. H., Jeffrey, K. R., Bloom, M., Valic, M. I., and Higgs, T. P., Chem. Phys. Lett., 1976, 42, 390.
7. Raleigh, D. P., Olejniczak, E. T., and Griffin, R. G., J. Magn. Reson., 1989, 81, 455.
8. English, A. D., Gardner, K. H., Schadt, R. J., Cain, E. J., Gabara, V., and Allen, S. R., Polym. Prepr., 1992, 33, 82.
9. English, A. D., Gardner, K. H., Schadt, R. J., Cain, E. J., Gabara, V., and Allen, S. R., Macromolecules, 1991, 24, 3721.
10. Cain, E. J., Gardner, K. H., Gabara, V., Allen, S. R., and English, A. D., Polym. Prepr., 1990, 31, 518.