ANL/CHM/CP--90634
CONF-960784--6

RECEIVED

SFP 19 1996

OSTI

Convenient synthesis of bis(benzo)-fused BEDT-TTF and higher homologues —
New electron donor molecules for organic charge transfer salts and "molecular rulers"

James P. Parakka, Aravinda M. Kini and Jack M. Williams
*Chemistry and Materials Science Divisions, Argonne National Laboratory,
9700 South Cass Avenue, Argonne, IL 60439, USA**

Abstract

A convenient synthesis of bis(benzo)- and bis(naphtho)-fused bis(ethylenedithio)tetrathiafulvalene (BEDT-TTF or ET) derivatives, employing the [4+2] cycloaddition reaction of oligo(1,3-dithiole-2,4,5-trithione) with appropriate alkenes as a key step, is presented.

Keywords: Organic superconductors, molecular rulers, BEDT-TTF or ET derivatives, heterocycle synthesis, coupling reactions.

1. Introduction

Among the number of tetrachalcogenafulvalenes employed as π donors for organic superconducting salts, bis(ethylenedithio)tetrathiafulvalene (BEDT-TTF or ET) **1** has been, by far, the most promising. A substantial number of cation-radical salts of ET have exhibited superconductivity, which to a large measure is due to the ability of ET molecules to engage in intermolecular inter-stack and intra-stack S...S interactions leading to quasi-two-dimensional band electronic structures [1,2]. Enlargement of the unit cell of isostructural ET salts, achieved by use of large charge-compensating anions, has been the most successful guiding principle to achieve higher superconducting transition temperatures (T_c) [2,3]. Alternatively, lengthening the ET donor molecule could also lead to a larger unit cell volume, and in salts with proper packing motifs and quasi-two-dimensionality, higher T_c s might be realized. Replacement of the terminal 1,2-ethanedithiol groups in ET with fused aromatic rings is expected to enlarge the unit cell volume, in addition to the attendant possibility of aromatic π - π interactions leading to new molecular packing motifs. To this end, the synthesis of dibenzo-ET **2** and dinaphtho-ET **3** derivatives was accomplished. The preparation of the dibenzo-ET derivative has been reported recently starting from 1,2-dimercaptobenzene in five steps, involving a low yielding cyclization step, with an overall yield of less than 4% [4]. A convenient and more general synthetic

methodology was thus needed for the preparation of **2** and the hitherto unknown dinaphtho-ET **3** for our studies as potential donors molecules for superconducting salts and for their possible applications in the design of "molecular rulers" [5].

2. Results and Discussion

The synthesis of the target molecules **2** and **3** was achieved by use of the trithione oligomer, oligo(1,3-dithiole-2,4,5-trithione) **4** [6] as the common starting material. Oligomer **4** is known to undergo thermal depolymerization at *ca.* 100°C and present itself as an effective 4 π component in pericyclic Diels-Alder reactions [6,7]. Scheme I outlines the synthesis of the dibenzo-ET derivative **2** wherein the key step is the [4+2] cycloaddition of 1,3-cyclohexadiene with the trithione derived from oligomer **4**. Aromatization of the resulting adduct **5** with DDQ in boiling toluene yielded the 4,5-benzenedithio-1,3-dithiole-2-thione **6**. Oxidation of thione **6** to the carbonyl

* Work at Argonne National Laboratory is sponsored by the U. S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences, under Contract W-31-109-ENG-38.

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

derivative 7, employing mercuric acetate in chloroform/acetic acid at room temperature, followed by phosphite coupling afforded 2. Our route to the preparation of dibenzo-ET is a far more convenient and efficient method (overall yield of ca. 30%) than the recently reported synthesis [4]. Furthermore, the Diels-Alder protocol provides a general methodology for the preparation of a variety of ET derivatives [6].

Scheme I

Scheme II

The Diels-Alder reaction of the oligomeric trithione was further exploited in the synthesis of the higher homologue, viz. the dinaphtho-ET 3 (Scheme II). Cycloaddition reaction of 4 with 1,4-dihydronaphthalene-1,4-endoxide (as a 2π component) in refluxing toluene resulted in the formation of the endoxide adduct 8. Subsequent aromatization of 8 with polyphosphoric acid gave the thione 9. Conversion of thione 9 to the carbonyl derivative 10, employing mercuric acetate in chloroform/acetic acid, followed by triethylphosphite-mediated coupling of 10 yielded the dinaphtho-ET 3. The overall yield of 3 from the above four steps was ca. 10%. Studies on the electronic behavior of the aromatic ring-annulated ET derivatives are in progress.

3. Conclusions

The synthesis of two examples of bis(areno)-fused ET derivatives, viz. dibenzo-ET 3 and dinaphtho-ET 4 has been accomplished by a general and convenient method taking advantage of the facile [4+2] cycloaddition reaction of the known oligo(1,3-dithiole-2,4,5-trithione) 4 with appropriate dienophiles.

References

- [1] J.M. Williams, A.J. Schultz, U. Geiser, K.D. Carlson, A.M. Kini, H.H. Wang, W.-K. Kwok, M.-H. Whangbo and J.E. Schirber, *Science* 252 (1991) 1501.
- [2] J.M. Williams, J.R. Ferraro, R.J. Thorn, K.D. Carlson, U. Geiser, H.H. Wang, A.M. Kini and M.-H. Whangbo, *Organic Superconductors (Including Fullerenes), Synthesis, Structure, Properties and Theory*, Prentice Hall, Englewood Cliffs, NJ, 1992.
- [3] (a) J.M. Williams, H.H. Wang, T.J. Emge, U. Geiser, M.A. Beno, K.D. Carlson, R.J. Thorn, A.J. Schultz and M.-H. Whangbo, *Prog. Inorg. Chem.* 35 (1987) 51. (b) G. Saito, H. Urayama, H. Yamochi and K. Oshima *Synth. Met.* 27 (1988) A331. (c) A.M. Kini, U. Geiser, H.H. Wang, K.D. Carlson, J.M. Williams, W.K. Kwok, K.G. Vandervoort, J.E. Thompson, D.L. Stupka, D. Jung and M.-H. Whangbo, *Inorg. Chem.* 29 (1990) 2555.
- [4] H. Müller, H.P. Fritz, R. Nemetshek, R. Hackl, W. Biberacher and C.-P. Heidmann *Z. Naturforsch.* 47b (1992) 718.
- [5] J.M. Williams, *Mol. Cryst. Liq. Cryst.* 284 (1996) 449.
- [6] (a) O. Neilands, J. Kaicens and J. Kreicberga, U. S. S. R. Patent # SU 1428753, 1988 *Chem. Abstr.* 110 (1989) 95252k. (b) O. Neilands, J. Kacens and J. Kreicberga, *Zh. Org. Khim.* 25 (1989) 658. (c) N. Svenstrup and J. Becher, *Synthesis* (1995) 215.
- [7] V.Y. Khodorkovsky, J.Y. Becker and J. Bernstein, *Synthesis* (1992) 1071.