DOE/PC/91302--T2

**FINAL REPORT
DOE GRANT DE-FG-91PC91302**

PROJECT TITLE: HYDROTHERMAL REACTIONS OF FLY ASH

Paul W. Brown
136 Intercollege Materials Research Laboratory
The Pennsylvania State University
University Park, PA 16802
814-865-5352

PRINCIPAL PROJECT PERSONNEL

P.W. Brown is a professor of Materials Science and Engineering. The principal areas of his expertise are in cements, use of industrial by-products in cement and concrete, establishing the long-term stabilities of cementitious materials. Brown dedicates about 6 hours per week of his time to this program. This includes formulating research direction, discussion of research results with students, and co-authoring research papers. Brown has a B.S. in Chemistry, a M.S. in Metallurgy and a Ph.D. in Materials Science. Prior to joining the faculty at Penn State in 9/87, Brown, was a Research Materials Engineering in the Building Materials Division at NBS (now NIST).

W. Ma obtained a Ph.D. in Materials with support from this program. He has a B.S. in Cement Technology from China and an M.S. in Materials from Penn State. This program provided support for his graduate assistantship and his research activities were entirely devoted to it.

John Dumm obtained an M.S. in Ceramics with support from this program. He holds a B.S. from Penn State. This program provided partial support for his graduate assistantship and his research activities were partially devoted to it.

Paul Rehrig obtained a B.S. in Ceramics. He carried out a Senior Thesis related to this program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

PROJECT OVERVIEW

Objectives

The reactions which occur when fly ash is treated under hydrothermal conditions were investigated. This was done for the following primary reasons. The first of these is to determine the nature of the phases that form, to assess the stabilities of these phases in the ambient environment and, finally, to assess whether these phases are capable of sequestering hazardous species. The second reason for undertaking this study was whether, depending on the composition of the ash and the presence of selected additives, it would be possible under hydrothermal conditions to form compounds which have cementitious properties.

Formation of four classes of compounds, which bracket likely fly ash compositional ranges, were selected for study. The classes are calcium silicate hydrates, calcium selenates, and calcium aluminosulfates, and silicate-based glasses. Specific compounds synthesized were determined and their stability regions assessed. As part of stability assessment, the extent to which selected hazardous species are sequestered was determined. Finally, the cementing properties of these compounds were established.

Significance to the Fossil Energy Program

In excess of 50 million tons of fly ash are generated annually in the United States. Because of the large amount of material generated, there is continuing interest in establishing ways in which fly ash may be used and a variety of uses have been identified. These include use as a filler for rubber, as a filler in asphaltic shingles and asphaltic concrete, and use as a pozzolan in portland cement concrete. However, none of these end uses has had a major effect on reducing ash disposal problems and none is likely to show substantial growth. In addition to the costs of disposal of large amounts of a material considered innocuous, there is continuing concern that certain fly ashes may also be hazardous. Identification of additional means to facilitate the use of fly ash and to avoid classification as hazardous waste would appear to be desirable. One way in which the potential uses of fly ash might be expanded and possible disposal hazards minimized is by specifically changing both the physical and chemical properties of the ash. However, considering the amount of material in question, a number of factors must be considered in estimating whether a particular process is practical. These include the energy requirements of the process, whether sophisticated equipment requiring a large capital investment would be required and, finally, whether the process was sensitive to compositional variations in the ash.

The results obtained in this program have demonstrated that mild hydrothermal conditions can be employed to improve the reactivity of fly ash. Such improvements in reactivity can result in the formation of monolithic forms which may exhibit suitable mechanical properties for selected applications as building materials. If the ashes involved are considered hazardous, the mechanical properties exhibited indicated the forms could be handled in a manner which facilitates their disposal.

Relationship to other DoE Projects

The generic aspects of this program apply to both "conventional" fly ash as well as to the ashes generated in clean coal technologies.

Project History

This grant was initiated on Oct. 1, 1991. It was scheduled for completion on Mar. 17, 1994. However, a one year no-cost extension was obtained. The total grant amount was \$200,000.

Work Done and Conclusions

The emphasis of the work done has been to determine the reactivities of two ashes believed to be representative of those generated. A bituminous ash and a lignitic ash have been investigated. The reactions these ashes undergo when subjected to mild hydrothermal conditions were explored. The nature of the reactions which the ashes undergo when alkaline activators, calcium hydroxide and calcium sulfate are present was also investigated. It was determined that calcium silicate hydrate, calcium aluminate hydrate, and the calcium sulfoaluminate hydrate ettringite form under these conditions. It appears $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 3\text{CaSO}_4\cdot 32\text{H}_2\text{O}$ (ettringite) formation needs to be considered in ashes which contain significant amounts of sulfate. Therefore the stability region for ettringite was established. It was also determined that calcium silicate hydrate, exhibiting a high internal surface area, will readily form with hydrothermal treatment between 50° and 100°C. This phase is likely to have a significant capacity to take up heavy metals and oxyanions and this ability is being explored.

Pore Structure

The nature of the pore structure which develops when low lime fly ash reacts with $\text{Ca}(\text{OH})_2$ and $\text{CaSO}_4\cdot 2\text{H}_2\text{O}$ under hydrothermal treatment has been investigated. The nitrogen adsorption-desorption isotherms of hydrothermally treated samples of fly ash and activated fly ash were analyzed. X-ray diffractometry was used to characterize the hydration products and SEM was used to analyze microstructure. The shapes and sizes of the hysteresis loops of isotherms and the pore size distribution data indicated the pore structure of samples were compressed primarily as wedge-shaped pores with open ends. The surface area obtained when fly ash reacted with $\text{Ca}(\text{OH})_2$ is 33.4 m²/g under hydrothermal treatment at 100°C, while that of untreated fly ash is only 1.3 m²/g. The surface area of fly ash after reaction with $\text{CaSO}_4\cdot 2\text{H}_2\text{O}$ is 2.9 m²/g. For fly ash treated with $\text{Ca}(\text{OH})_2$, the volumes of the pores with radii of 19Å increased with increasing temperature of thermal treatment. Calcium silicate hydrate, calcite and anhydrite formed at different temperatures. Calcium silicate hydrate was found to be responsible for the change of the surface area of fly ash with $\text{Ca}(\text{OH})_2$ treatment at elevated temperature.

Hydrothermal Phase Stability

Establishing phase formation in the system $\text{CaO}\text{-}\text{Al}_2\text{O}_3\text{-}\text{SiO}_2\text{-}\text{Na}_2\text{O}\text{-}\text{H}_2\text{O}$ is extremely important because of its significance in the treatment of fly ash-related waste products. It provides a theoretical guidance to assess the stabilities of the phases that form in the system in the ambient environment and to assess whether these phases are capable of sequestering hazardous species.

The hydrothermal behavior of model systems for fly ash are being studied. These were synthesized using pure starting materials [colloidal silica (SiO_2), lime (CaO) and alumina (Al_2O_3)], so that the exact compositions of the mixtures could be specified. Minor constituents, such as Fe_2O_3 , MgO , K_2O , and TiO_2 were ignored. Starting materials were combined with deionized water or NaOH solution and hydrothermally treated for 24 hours under saturated steam pressure using a tubular pressure vessel. Crystalline phases are being observed using the X-ray diffraction

for samples treated at temperature ranging from 25° to 180°C in these systems. Hydrated calcium silicate (C-S-H) was formed over the whole temperature range from 25° to 180°C. For samples reacted in the presence of NaOH solution a similar observation can be made. Thus, it can be concluded that NaOH activation of a mixture of the above compounds simulating fly ash in composition is not required for reaction in the temperature range of interest. Calorimetric analyses have shown the rates of heat evolution during the first one and a half hours at 25° and 38°C. Only single heat evolution peaks, which occur immediately after mixing, were observed. The curves again suggests that sodium hydroxide does not provide a means of activating this material. The variations in pH show that a decrease occurs for both cases from 25° to 180°C. This allows an assessment of the stabilities of C-S-H formed in the system in the range of pH values and temperatures.

Heavy Metal Uptake

Sr, Ag, and As

The objective of this aspect of the program was to determine the equilibrium conditions achieved during the hydrothermal processing of coal fly ash in the presence of heavy metals. The specific equilibrium conditions are those achieved between the calcium silicate or calcium aluminate phases and the heavy metals present. To decrease the time required to reach equilibrium, the research focused on the determination of the solid phases that form when calcium aluminate hydroxide (C_3AH_6) equilibrated with the Sr ion. This was selected as a model system because Sr exhibits relatively low toxicity. A variety of strontium aluminates were prepared and analyzed by X-ray diffraction. However, it was determined that carbonation was a problem and the actual phases were carbonate-substituted calcium, strontium aluminate hydrates. Work was also done on Ag cation and on AsO_4 anion. Ag did not appear to substitute into calcium aluminates and arsenate formed a variety of compounds with calcium aluminates.

Calcium Selenates

Selenium in the biosphere is a continuing environmental concern. This is particularly true in agriculture. Toxic effects of high Se have been identified in grazing livestock. Conversely, low Se concentrations in soils have resulted in selenium deficiencies in livestock. Because of such toxicity problems, the delivery of Se to the environment is a major concern. Of the selenium species, only SeO_3^{2-} and SeO_4^{2-} are significantly soluble; the selenides and elemental selenium are, in comparison, insoluble.

An important industrial origin of selenium is in the ash formed during the combustion of coal, and Se is present in the ash formed in the combustion of oil and municipal refuse. The ability of Se from ash to enter the environment has been well demonstrated. In particular, fly ash from coal combustion is used in significant amounts in cement and concrete. Because of this use, selenium becomes widely distributed. As a consequence, the fate of Se species in cement is of concern because of the significant use of coal fly ash in this way. These studies indicate the importance in elucidating the chemistry of the selenite and selenate species derived from ashes.

In the course of investigating the behavior of selenium in cementitious systems it was found the chemistry of the system $CaO-SeO_2-H_2O$ was poorly established. Prior work studied the phases formed in the acidic region of this system and characterized them by X-ray powder diffraction and infrared analysis. However, the results are of uncertain quality. IR spectra and

thermal decomposition behavior of a variety of alkaline earth selenites, including $\text{CaSeO}_3 \cdot \text{H}_2\text{O}$ and $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$ have been determined and the crystal structure parameters for these phases and for the compound $\text{Ca}_2(\text{HSeO}_3)_2(\text{Se}_2\text{O}_5)$ have been reported. However, there does not appear to have been a study which systematically determined the compositions of calcium selenate phases which form at low temperature and their diffraction patterns, thermal stabilities, and morphologies. The synthesis and characterization of the hydrated phases $\text{CaSeO}_3 \cdot \text{H}_2\text{O}$, $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$, $\text{Ca}_2(\text{SeO}_3)(\text{Se}_2\text{O}_5)$, and $\text{Ca}_2(\text{HSeO}_3)_2(\text{Se}_2\text{O}_5)$ were carried out.

Four calcium selenates were prepared and characterized. These were $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$, $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$, $\text{Ca}_2(\text{HSeO}_3)_2(\text{Se}_2\text{O}_5)$, and $\text{Ca}_2(\text{SeO}_3)(\text{Se}_2\text{O}_5)$. $\text{CaSeO}_3 \cdot \text{H}_2\text{O}$ and $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$ are the stable calcium selenites at 23°C , while $\text{CaSeO}_3 \cdot \text{H}_2\text{O}$, $\text{Ca}_2(\text{SeO}_3)(\text{Se}_2\text{O}_5)$ and $\text{Ca}_2(\text{HSeO}_3)_2(\text{Se}_2\text{O}_5)$ are stable at 80°C . Each of these solids eventually forms CaSeO_3 with heating.

Three types of decomposition phenomena occur in the formation of CaSeO_3 . One is the loss of waters of hydration. This occurred as $\text{CaSeO}_3 \cdot \text{H}_2\text{O}$ converted to CaSeO_3 and $\text{Ca}(\text{HSeO}_3)_2 \cdot \text{H}_2\text{O}$ converted to $\text{Ca}(\text{HSeO}_3)_2$. The latter calcium selenate was observed to form as an intermediate, but it was not characterized in this study. The second decomposition path observed involves a condensation reaction forming Se_2O_5 as compounds containing structural water decompose. An example of this is the decomposition of $\text{Ca}(\text{HSeO}_3)_2$ to $\text{Ca}_2\text{Se}_2\text{O}_5$. Finally, decomposition reactions were observed in which SeO_2 vapor was evolved resulting in the formation of CaSeO_3 . This occurred as $\text{Ca}_2\text{Se}_2\text{O}_5$ decomposed to CaSeO_3 .

Formation and Stability of Sulfate-Substituted Calcium Aluminate Hydrate

The constituents of ettringite are present in fly ashes. The conditions under which ettringite forms, or is stable, are of importance with regard to the properties exhibited when a fly ash is incorporated into concrete. In particular ettringite formation effects setting of cement and the durability of concrete. Ettringite stability is most frequently considered with respect to the availability of sulfate and it is generally accepted that ettringite formation in cement only occurs when some form of calcium sulfate is present. Once the calcium sulfate initially present has been consumed, ettringite begins to decompose and monosulfate forms in its place. However, the stability of ettringite is influenced by temperature and solution chemistry and there are conditions under which ettringite does not form during early hydration. For example, if hydration is carried out above a certain temperature, ettringite formation is not observed. Rather, it may be delayed, occurring only after an extended period of months to years in duration. The stability of ettringite and the conditions likely to influence the delayed formation of ettringite were considered in this study.

Ettringite was formed during the hydration of C_3A with gypsum at temperatures from 25° to 80°C . Ettringite formation was retarded when hydration was carried out in KOH solutions whose concentrations were as high as 2.0 M. Solutions with KOH concentrations between 0.5 and 1.0 M have the greatest retarding effect. In spite of the retarding effect of KOH , ettringite was observed to form at 80°C in 2.0 M KOH . Hydration in solutions with KOH concentrations greater than 0.5 M also produced syngenite.

When C₃A is hydrated with gypsum in the presence of C₃S, ettringite, CSH and CH were formed in the absence of KOH. Hydration of 80% C₃S, 10% C₃A and 10% gypsum in 0.5 M KOH solution was adequate to essentially eliminate the formation of ettringite. Rather, calcium hydroxide and CSH containing sulfate and aluminate were formed. Thus the preferred phases when hydration occurs in KOH are CSH and CH; whereas the preferred phases for hydration in water are CSH, CH, and ettringite. Thus, the elimination of ettringite formation by high temperature curing requires the presence of hydrating C₃S.

The observations made in studying these model systems are used as the basis for the development of a mechanism of delayed ettringite formation in cement. They are also used in describing a relationship between delayed ettringite formation and the alkali-silica reaction.

In addition to the silicate phases, the aluminate and aluminoferrite phases are the major constituents of portland cement. The former, which include impure forms of tricalcium silicate and dicalcium silicate, are acknowledged as the principal binder phases typically comprising approximately 75 weight percent of the material. The aluminate and aluminoferrite phases, often referred to as interstitial phases, fuse at lower temperatures than the silicates, and exhibit a broader range of compositions. Cubic C₃A* can accommodate up to about 2.4% Na₂O while up to 5.7% can be incorporated into a monoclinic polymorph. In addition to substitution by sodium, significant substitution by Fe₂O₃ and SiO₂ may also occur.

(*In shorthand notation commonly used for cements: C₃A=3CaO·Al₂O₃;
C₄AF=4CaO·Al₂O₃·Fe₂O₃; H=H₂O; CsH₂=gypsum=CaSO₄·2H₂O;
CaSO₄·1/2H₂O=calcium sulfate hemihydrate which is referred to as hemihydrate)

The ferrite phase, while often expressed as C₄AF*, does not have a fixed composition. Rather, it is a solid solution which exists over the compositional range Ca₂Al_xFe_(2-x)O₅ with x > 0.6. However, a composition typical of the ferrite phase found in clinkers is Ca₂AlFe_{0.6}Si_{0.15}Ti_{0.05}O₅. This is significantly different from C₄AF. In spite of these variations, the aluminate and aluminoferrite phases are commonly expressed in terms of their ideal compositions: 3CaO·Al₂O₃ and 4CaO·Al₂O₃·Fe₂O₃.

Various studies have been carried out to establish the kinetics of C₃A hydration in the presence of calcium sulfates. While views may differ with regard to mechanistic details, each of these investigations has reached the conclusion that ettringite formation is diffusionally controlled. Most recently, developed models describe the hydration of C₃A and of C₃A in the presence of gypsum based on the rate of heat release and hydration is considered to occur in three stages. During the first stage, the rate of heat evolution continuously decreases as hydration is controlled by diffusion through thickening layers of ettringite which surround the C₃A grains. In the second stage of reaction, ettringite is converted to monosulfate and diffusion occurs through layers of decreasing thickness. In the third stage of hydration, the rate of heat release is controlled by diffusion through layers comprised of the monosulfate phase and calcium aluminate hydrates all of which exhibit a hexagonal plate-like morphology.

Relatively few investigations have been carried out to establish the kinetics of C₄AF hydration in the presence of calcium sulfates. Heat evolution curves for the hydration C₄AF with

gypsum appear similar to those observed for the hydration C_3A with gypsum. As with the hydration of C_3A , the rate of C_4AF hydration with gypsum appears to be diffusionally controlled.

It is generally accepted that C_3A is the most reactive of the major cement phases and as a consequence its rate of reaction must initially be retarded by ettringite formation. The following relative rates of reactivity are typical of those reported for pure phases and in cement, respectively: $C_3A > (C_3A + CsH_2) > C_3S > C_2S$; $C_3A > \text{alite} > \text{ferrite} > \text{belite}$. It is anecdotally accepted that, because the ferrite phase in cement exhibits low hydraulic reactivity, C_4AF is unreactive. However, with the exception of one study, investigations rigorously comparing the rates of hydration of C_3A and C_4AF appear not to have been carried out. Thus, a study was carried out to compare the rates of hydration of C_3A and C_4AF and to quantify the relative differences in their rates of reaction using heat evolution as the criterion for reactivity.

Hydration reactions of C_3A and C_4AF with calcium sulfate hemihydrate and gypsum were investigated and the kinetics of the reactions compared. The rates of C_3A and C_4AF hydration, as determined by heat evolution, vary depending on whether the sulfate-containing reactant is gypsum or calcium sulfate hemihydrate. The following sequence of reactions involving C_4AF occurs when hemihydrate is the reactant: gypsum formation during the first hour, ettringite formation between 20 and 36 hours, and the conversion of ettringite to monosulfate over a period of about 12 hours. Monosulfate formation initiates prior to the complete consumption of gypsum. The onset of this conversion occurs at a shorter hydration time when hemihydrate is a reactant and the total amount of heat evolved is lower. The hydration reactions in saturated calcium hydroxide solution occur more slowly than those in water.

Based on heat liberation, C_4AF reacts at a much higher rate than C_3A . Ettringite formation occurs during the first 8 to 9 days of C_3A hydration. Once the gypsum is consumed, ettringite converts to monosulfate during two additional days. Compared to gypsum, hemihydrate decreases the rates of hydration of both C_3A and C_4AF . The effects on the hydration characteristics of C_4AF are significant.

The hydration of C_3A with gypsum in water, in saturated $Ca(OH)_2$ solution, and in 0.3 M NaOH solution were compared. Heat evolution is the lowest for hydration in 0.3 M NaOH. The onset of monosulfate formation occurs prior to the complete reaction between gypsum and C_3A in the NaOH solution.

Ash Reactivity

Hydration heat is an important factor affecting the setting and characteristic behavior of portland cements. Temperature variation during hydration may cause thermal stresses which can result in crack formation. Partial replacement of portland cement by fly ash, silica fume or slag affects both the rate and the extent of heat generation, and it is believed that these additions can alter the heat evolved by portland cements during hydration.

Various studies have investigated the nature of the hydration products formed from portland cement during curing at elevated temperature. It has been suggested that a C-S-H phase with a lower water content and higher C/S ratio was formed at elevated temperatures. Moreover, the proportions of foreign ions (Al^{+3} , Fe^{+3} , SO_4^{-2}) incorporated in the C-S-H increase with

increasing hydration temperature. Hydration temperature also influences the porosities and pore size distributions in the hydrated material formed. An increase in curing temperature from 50° to 50°C results in increased porosity and could have a deleterious effect on concrete durability.

Temperature-dependent changes may affect both the silicate and the aluminate phases in cement. A number of investigators have pointed out that ettringite becomes unstable at elevated temperatures and AFm is formed instead. However, it has also been reported that the kinetics of ettringite formation exhibited minimal temperature dependence over the range from 50° to 70°C.

It is well known that many natural pozzolans demonstrate satisfactory performance in blended cements. Low-calcium fly ash is widely recognized as a good pozzolan; beneficial effects produced are consumption of $\text{Ca}(\text{OH})_2$ and a reduction in C_3A content in blended cement due to dilution. Reduction in porosity by C-S-H (II) formation and protection of cement compounds unstable in sulfate environments are also beneficial effects associated with blended cements. Effects of curing temperature on properties of blended cement have also been extensively reported in the literature. It is well recognized that low-calcium fly ash influences cement hydration and reduces the heat evolution when it is used as a partial cement replacement.

Although high pozzolanic activity of silica fume has been described, it has also been reported that silica fume exhibits relatively low pozzolanic activity. Silica fume has been used as an early reactive filler in blended cements in combination with fly ash, with slowly reactive slag, or with inert material such as quartz. The addition of silica fume to portland cement was found to improve both rheology and strength development.

Granulated blastfurnace slag is hydraulic in itself but contains more SiO_2 and less CaO than portland cement. Although slags usually react more slowly than portland cement, they produce compositionally similar hydrates: C-S-H and sulfoaluminates. Major differences are in the rates and the intensities of the hydration reactions. One result of these differences is that slag cements produce microstructures quite different from those of portland cement pastes.

The qualitative differences in the behavior of these mineral admixtures are well recognized. Their quantitative effects on hydration are less well understood. This is particularly important with respect to predicting strength gain. Calculation of maturity depends on the use of a value for an "activation energy" which indicates the temperature dependence of strength gain. However, activation energies have not been well established for blended systems. Thus it was the purpose of the research to compare the activation energies obtained by measuring the heat evolution characteristics of blended cements containing fly ash, silica fume, and slag.

Because portland cement is the major component in all blended cements, heat evolution during its hydration was studied. The heat evolution characteristics of blended cement containing fly ash, silica fume and slag individually at various temperatures are determined. Using these data, comparisons were made to determine the extent to which temperature influenced reactivity. The hydration behavior of blended cements containing fly ash, silica fume, and granulated blastfurnace slag over the temperature range of 10° to 55°C was studied by isothermal calorimetry. The rates of heat evolution during the first 24 hours of hydration were examined. The results were analyzed to determine the kinetics of hydration of portland and blended cements. Relationships between the

reactivities of these blended cements and the curing temperature were established. The results show that the rates of hydration reactions increased with an increase in temperature in all instances. Comparison among the blends containing fly ash, silica fume and slag was made to establish activation energies for the hydration reactions. E_a values obtained were 39.0, 26.7, 30.4 and 49.3 KJ/mol for portland cement, fly ash, silica fume, and slag blended cements, respectively. The relatively constant E_a values for the blended cements may be related to diffusionally controlled hydration of the mineral admixtures.

Glass Studies

In addition to the above task areas, the ability of the glassy constituents of fly ashes to crystallize was studied. Except for consumable items, this study was carried out at no cost to the program as a senior thesis project. The crystallization kinetics of high iron-content glasses and reagent grade glass modifiers were investigated. The soil examined formed a glass when melted by itself. The model system $K_2O-Fe_2O_3-SiO_2$ was studied in particular. SiO_2 is the major constituent of the soil and the proportion of K_2O modifier was held at a constant 10 weight percent. The melts exhibited increasing extents of phase separation and devitrification with increasing proportions of ferric oxide. Time-temperature-transformation (TTT) diagrams were constructed to determine the temperature dependence of the crystallization kinetics. Annealing low and high Fe_2O_3 compositions indicated the samples readily devitrified. X-ray diffraction analyses showed leucite was the major crystalline phase at low Fe_2O_3 contents. For compositions high in Fe_2O_3 , magnetite was the major phase with some leucite appearing as a secondary phase. Augite formed at both low and high Fe_2O_3 contents in conjunction with the other phases present. The results of the investigation establish the phase stability regions involving these phases.

PROJECT OUTPUT

Publications

Ten publications were produced as a result of the research performed in this program. Each of these publications has been published in, or submitted to, a peer-reviewed journal.

1. P.W. Brown and J.V. Bothe, Jr., "The Stability of Ettringite," *Adv. Cem. Res.* **5**(18), 47-63 (1993).
2. E. Gruszczynski, J.V. Bothe, and P.W. Brown, "Ettringite Formation at Elevated Temperatures," *Cem. Concr. Res.* **23**(4) 981-87 (1993).
3. K. Gergova, S. Eser, H.H. Scholbert, M. Klimkiewicz, and P.W. Brown, "Environmental scanning electron microscopy of activated carbon production from anthracite by one step pyrolysis-activation" *Fuel* **74**(7), 1042-48 (1995).
4. P.W. Brown, "The Kinetics of Tricalcium Aluminate and Tetracalcium Aluminoferrite Hydration in the Presence of Calcium Sulfate," *J. Am. Ceram. Soc.* **76**(12), 2971-76 (1993).
5. W. Ma, D. Sample, R. Martin and P.W. Brown, "Calorimetric Study of Cement Blends Containing Fly Ash, Silica Fume, and Slag at Elevated Temperature," *ASTM J. of Cement, Concrete, and Aggregates* **16**, 93-99 (1994).
7. W. Ma, C. Lui, P.W. Brown and S. Komarneni, "Pore Structures of Fly Ashes Activated by $\text{Ca}(\text{OH})_2$ and $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$," *Cem. Concr. Res.* **25**, 417-25 (1995).
8. J.Q. Dumm and P.W. Brown, "Synthesis and Characterization of Calcium Selenate Hydrates," *J. Crystal Growth*, submitted.
9. W. Ma and P.W. Brown, "Hydrothermal Synthesis of Tobermorite from Fly Ashes," *Adv. Cem. Res.*, submitted.
10. P. Rehrig, J.Q. Dumm, and P.W. Brown, "Crystallization of High Iron-Content Vitriified Waste," in prep (for *J. Am. Ceram. Soc.*).

In addition, the support provided by the program has permitted the PI to edit the following volume whose topical content is in an area related to the program:

Cement Manufacture and Use, P.W. Brown, Ed., Engr Foundation, NY (1994) 317 pp.

Presentation titles:

Incorporation of Metals in Ceramics and Glasses, J.Q. Dumm, P.W. Brown, and W. Richmond, American Ceramic Society (1993)

Reactivity of Fly Ash with Alkaline Activators at Different Temperatures, W. Ma and P.W. Brown, American Ceramic Society (1993)

The Chemistry of Ettringite Formation. This was given at a workshop entitled: *Utilization of Fly Ashes and Other Coal Combustion By-Products*, Lexington KY (1994).