SAND98-2192C
SAND--98-2192C
CONF-981046--

RADIATION DAMAGE MEASUREMENTS IN ROOM TEMPERATURE SEMICONDUCTOR RADIATION DETECTORS

RECEIVED

OCT 02 1998

Larry A. Franks¹, Bruce A. Brunett^{1,2}, Richard W. Olsen¹, David S. Walsh³, Gyögy Vizkei^{3,5},
Jacob I. Trombka⁴, Barney L. Doyle³, and Ralph B. James¹

1. Sandia National Laboratories, Livermore, CA 94550
2. ECE Department, Carnegie Mellon University, Pittsburgh, PA 15213
3. Sandia National Laboratories, Albuquerque, NM 87185
4. NASA Goddard Space Flight Center, Greenbelt, MD 20771
5. Idaho State University, Pocatello, ID 83209

Abstract

The literature of radiation damage measurements on cadmium zinc telluride (CZT), cadmium telluride (CT), and mercuric iodide (HgI_2) is reviewed and in the case of CZT supplemented by new alpha particle data. CZT strip detectors exposed to intermediate energy (1.3 MeV) proton fluences exhibit increased interstrip leakage after 10^{10} p/cm² and significant bulk leakage after 10^{12} p/cm². CZT exposed to 200 MeV protons shows a two-fold loss in energy resolution after a fluence of 5×10^9 p/cm² in thick (3 mm) planar devices but little effect in 2 mm devices. No energy resolution effects were noted from moderated fission spectrum of neutrons after fluences up to 10^{10} n/cm², although activation was evident. Exposures of CZT to 5 MeV alpha particle at fluences up to 1.5×10^{10} α /cm² produced a near linear decrease in peak position with fluence and increases in FWHM beginning at about 7.5×10^9 α /cm². CT detectors show resolution losses after fluences of 3×10^9 p/cm² at 33 MeV for chlorine-doped detectors. Indium doped material may be more resistant. Neutron exposures (8 MeV) caused resolution losses after fluences of 2×10^{10} n/cm². Mercuric iodide has been studied with intermediate energy protons (10 to 33 MeV) at fluences up to 10^{12} p/cm² and with 1.5 GeV protons at fluences up to 1.2×10^8 p/cm². Neutron exposures at 8 MeV have been reported at fluences up to 10^{15} n/cm². No radiation damage was reported under these irradiation conditions.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

Sandia is a multiprogram laboratory
operated by Sandia Corporation, a
Lockheed Martin Company, for the
United States Department of Energy
under contract DE-AC04-94AL85000.

Introduction

The well documented radiation damage in cryogenic germanium and silicon detectors (refs 1,2) at relatively modest charge particle fluences has prompted interest in the response of the room temperature semiconductor materials now under development. Radiation damage in semiconductor detectors causes degradation of energy resolution, increased leakage current, and reduction of the peak position. Depending on the elemental constituents, activation may also occur in the case of neutron exposures. Exposure parameters affecting the response of materials to radiation fields include the fluence level, flux, incident energy, detector bias, and detector temperature. In addition to the base constituents, trace contaminants as well as detector dimension can also affect radiation response.

In the case of cryogenic silicon, significant energy resolution losses occur at about 10^{12} n/cm² (ref. 1) with leakage current and pulse height changes after 5×10^{11} protons/cm². Planar germanium detectors exhibit significant resolution losses after 10^9 n/cm². Coaxial (n-type) are appreciably more resistant to neutrons than p-type (ref 2). Coaxial (p-type) germanium detectors begin to show resolution losses at about 2×10^7 p/cm² while in n-type coaxial (reverse electrodes) detectors; resolution losses appear at about 2×10^8 p/cm². Despite the susceptibility of germanium to radiation damage, thermal annealing methods have been developed to mitigate, if not reverse, the symptoms of high fluence exposures.

In this paper we report the results of a survey of radiation damage studies in the room temperature semiconductor materials: cadmium zinc telluride (CZT), cadmium telluride (CT), and mercuric iodide (HgI₂). Also reported are new 5 MeV alpha particle data on CZT including α response maps showing material inhomogeneities.

Methods

Survey data were obtained through a literature search using the computer databases INSPEC and CALPLUS together with DOE archives. In all, more than 300 abstracts were reviewed. The review was confined to the materials cadmium zinc telluride, (CZT), cadmium telluride (CT), and mercuric iodide (HgI₂), the most promising of the wide-band gap materials now under development.

Alpha particle exposures were made with He²⁺ ions from the Sandia Tandem Van de Graaff. The flux was maintained at 2.8×10^7 α /cm²-sec and measured by means of a scalar connected to the output of the detector under test. The beam spot size was 1 micron in diameter. Exposures were made in vacuum and carried out by scanning the beam over the surface of the detector. This procedure provided both effects data as well as homogeneity maps of the detector surface. Gross positioning was accomplished with an x-y stage; fine adjustments, over a 250 micron by 250 micron area, were made with the accelerator's beam handling system.

Results

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

The radiation effect reported most frequently was the change in energy resolution, although changes in the leakage current and peak position shifts were sometimes cited. Energy resolution (ΔE) was determined in most cases by recording the spectrum of a monochromatic photon or alpha particle before and after exposure. Detector energy resolution is reported here in terms of the full width of a given spectral line at its half intensity point (FWHM). In general, neither the detector bias conditions nor the detector temperature were reported. Where available, this information is noted in this report. The results including the recently obtained α particle data are summarized in Tables 1-3.

Mercuric Iodide

The results of this investigation are summarized in Table 1. Proton exposures at 10, 10.7, 33, and 1500 MeV have been reported at fluences ranging from 1.2×10^8 protons/cm² (1500 MeV) to 10^{12} protons/cm² (10.7 MeV). Also reported were 8 MeV neutron exposures at fluences up to 10^{15} n/cm².

In 10.7 MeV protons exposures, no losses in energy resolution were found in the 5.9 KeV Mn - K α line in a group of 6 detectors following fluences up to 10^{12} p/cm² (ref 3). Similar results were reported (ref 4) for a single detector 0.4 mm thick in 5.5 MeV α peaks for 10 MeV protons at fluences up to 10^{10} p/cm²; the relative pulse height decreased by approximately 20% following exposure of 10^{11} p/cm², however. No resolution losses were found in a group of 3 detectors from 33 MeV proton exposures in 59.5 and 122 KeV photon peaks following fluences of up to 2.5×10^{10} p/cm² (ref 5).

A group of 4 detectors with an average active area of 6.4 mm² were exposed to a flux of 10^5 protons at 1.5 GeV (ref 6). The detectors, initially unbiased, exhibited anomalous leakage current after the first exposure of 2×10^6 protons/cm². Subsequent exposures were made under bias and the leakage remained stable. No loss in resolution was found in 5.9 KeV photon peaks following exposures up to 1.2×10^8 p/cm². Little effect was found in a single 50 mm² detector (active thickness .26 mm) from 8 MeV neutron exposures in 5.3 MeV α peaks after fluences up to 10^{15} n/cm² (ref 4). No data on effects from high-energy photon exposures were found.

TABLE 1.
Radiation Damage in HgI₂ Room Temperature Semi-Conductor Detectors

Material	Radiation	Effects	
HgI ₂	Proton.-10.7 MeV	No ΔE loss 10 ¹² p/cm ²	
	10.0 MeV	No effect 10 ¹⁰ p/cm ²	
	1.5 GeV	No ΔE loss to 1.2 x 10 ⁸ p/cm ²	
	33 MeV	No ΔE loss 2.5 x 10 ¹⁰ p/cm ²	
	Neutron- MeV	Little ΔE effect up to 10 ¹⁵ n/cm ²	
	Photon	No reported data	

Cadmium Telluride

Damage studies were found for proton, neutron, and photon irradiation. The results are summarized in Table 2. Proton exposures at 33 MeV were made on chlorine and indium-doped material (ref 5). This energy was selected so that the beam passed through the thickest samples (2.8 mm) and thus contributed no Bragg peak in the test samples. In chlorine-doped samples, the energy resolution in 59.5 and 122 KeV peaks degraded sharply after about 3 x 10⁹ protons/cm². There was some evidence of a slight resolution improvement at lower fluences. Evidence of detector thickness dependence in the resolution response was also noted. While quantitative data were not obtained for the single indium-doped device tested, the data suggests a higher degree of radiation resistance than with the chlorine-doped material. Neutron irradiations were reported at a mean energy of about 3 MeV (ref 7). Significant reductions in energy resolution were reported after about 5x10¹⁰ n/cm² in 5.5 MeV alpha spectra using a flux of 10⁸ n/cm²-s. Photon irradiations were reported using Co-60 (1.17 and 1.33 MeV) with the resolution monitored at 662 and 59.6 KeV (ref 8). Marked changes in peak shape were reported at both energies after exposure of several times 10⁵ R. No data were found at intermediate and low exposure levels.

TABLE 2.

Radiation Damage in CdTe Room Temperature Semiconductor Detectors

Material	Radiation/Energy	Effects	
CdTe	Proton 33 MeV	<u>Chlorine doped</u> — ΔE degradation after $\sim 3 \times 10^9$ p/cm ² . <u>Indium doped</u> — evidence of greater radiation resistance, no quantitative data	
	Neutron 3 MeV	p-type — increasing ΔE loss in 5.5 MeV α peaks at 2×10^{10} n/cm ²	
	Photon 1.25 MeV	Substantial ΔE loss @ 59.6 KeV after 10^5 R	

Cadmium Zinc Telluride

Radiation damage studies on CZT have been carried out with protons (1.3 and 200 MeV) and neutrons (moderated fission spectrum). The results of these studies are shown in Table 3. In a single detector with 1.3 MeV protons, the bulk leakage was found to increase significantly after 10^{12} p/cm² in a single unbiased $10 \times 10 \times 2$ mm³ strip detector (ref 9) The interstrip leakage increased significantly after about 10^{10} p/cm². No energy resolution data were reported.

Considerable work has been reported in the region of 200 MeV. In one study (ref 10) 2 and 3 mm thick planar detectors were irradiated with up to 5×10^9 p/cm² and resolution losses were found in the thicker devices (3 mm). The initial (unirradiated) FWHM values at 59.6 and 122 KeV of 3.2 KeV and 3.9 KeV, respectively, degraded to 4.1 and 4.3 after 10^9 p/cm² and to 6.2 and 9.2 KeV after 5×10^9 p/cm². The thinner device (2 mm) showed no degradation at either energy after like exposures, however. A downward shift in peak channel with increasing fluence was reported for both thick and thin detectors. The degradation in energy resolution is attributed to radiation induced electron trapping.

In a similar study, (ref 9), both strip and planar detectors were exposed to 200 MeV protons. The strip detectors ($15 \times 15 \times 2$ mm³) were exposed under bias to fluences from 10^8 to 5×10^9 p/cm². A small gain shift (3%) was noted after a fluence of 1×10^9 p/cm² and a significant shift (>25 %) after 5×10^9 p/cm². No consistent pattern of resolution degradation was found. The resolution of a single detector exposed to 5×10^9 p/cm² was unchanged at 59.6 KeV but significantly degraded at 122 KeV while small losses (and gains) were found at 1×10^8 and 1×10^9 p/cm². In this study, the outputs of three strips in each detector were summed; one detector was used for each fluence level ($1, 10, \text{ and } 50 \times 10^8$ p/cm²). Two planar devices ($10 \times 10 \times 2$ mm³ and $15 \times 15 \times 2$ mm³) were exposed to a fluence of 5×10^9 p/cm², one under bias the other unbiased. Gain shift and energy resolution were measured at photon energies of 14.4, 17.8, 59.6, and 122 KeV. Gain shifts were found at all energies in both biased and unbiased cases. Significant (>45%) resolution

losses were found at 59.6 and 122 KeV in the unbiased device. Minor changes (both positive and negative) were reported for the biased case.

Neutron irradiation with a moderated fission spectrum source (Cf-252) at fluences up to about 10^{11} n/cm² have been reported (ref 11) on a single detector. The detector 10 x 10 x 2 mm³ was biased during exposure. No resolution degradation was found at photon energies of 14.4, 26.3, 59.6, and 122 KeV for fluences up to 10^{10} n/cm². Significant resolution losses were found after 7×10^{10} n/cm², however. It is interesting to note that the resolution losses were largely recovered after 12 weeks of annealing at room temperature. Evidence of neutron activation, in the form of gamma-ray lines from cadmium and tellurium isotopes, was apparent at fluences beyond about 10^{10} n/cm². Although not reported, similar effects can be expected in CdTe.

TABLE 3.

Radiation Damage in Cadmium Zinc Telluride (CZT) Room Temperature Detectors

Material	Radiation/Energy	Effects	
CZT	Proton 199 MeV	onset of ΔE loss at 10^8 p/cm ² ; 2 fold increase in ΔE @ 5×10^9 p/cm ² (3mm thick)thick detector , little ΔE change in 2mm device -- Downward peak shift proportional to fluence in 2 mm and 3 mm devices	
	Protons 200 MeV	<u>Strip detector (biased)</u> >25% gain shift following 5×10^9 p/cm ² <u>Planar (biased)</u> -- Small ΔE effects, both positive and negative found @ 14.4, 59.6, and 122 KeV <u>Planar (unbiased)</u> - Large (>45%) ΔE losses following 5×10^9 p/cm ² exposure -- Gain shifts in both biased and unbiased detectors at 14.4, 17.8, 59.6, and 122 KeV	
	Proton 1.3 MeV	<u>2 mm thick strip detector (unbiased)</u> Bulk leakage increases after 10^{12} p/cm ² Interstrip leakage increases after 10^{10} p/cm ²	

TABLE 3. (continued)

Radiation Damage in Cadmium Zinc Telluride (CZT) Room Temperature Detectors

Material	Radiation/Energy	Effects	
CZT	Neutron Moderated Fission Spectrum	<u>Planar detection</u> -- No ΔE effects up to 10^{10} n/cm ² -- Measurable ΔE loss @ 10^{11} n/cm ² -- Activation emission (γ) at 10^{10} n/cm ²	
	Alpha 5 MeV	linear decrease in peak position with exposure beginning at 2.5×10^9 α /cm ² ΔE increases by 60% at 1.5×10^{10} α /cm ²	

The results of this review were supplemented with alpha particle irradiation. The exposures were made with 5 MeV He²⁺ ions produced in the Sandia Tandem van de Graaff and made on a single 3 x 3 x 2 mm³ CZT detector. The exposures were in vacuum over the region from 2.5×10^9 α /cm² to 1.5×10^{10} α /cm² by scanning the 1 micron diameter beam spot over the surface of the detector. The flux was maintained at approximately 2.8×10^7 α /cm²-sec by monitoring a scalar connected to the output of the detector. Alpha particle spectra obtained by integrating the pulses from a small irradiated area are shown in Figure 1. Plots of the resultant FWHM and the peak position are shown in figure 2. The data of Figure 2 show a near linear decrease in the peak position with fluence. The FWHM, after decreasing initially, increases by more than 60% after an exposure of 1.5×10^{10} α /cm². Variation in the response of the detector as measured by the α counts recorded as the detector was scanned are shown in figure 3. One notes a number of non-responding elements distributed through the sample including a band in the lower left. The cause of this effect is currently under investigation.

Summary And Conclusions

Knowledge of the radiation susceptibility of the leading room temperature semiconductor detectors CZT, CdTe, and HgI₂, is incomplete. Factors known to be of significance in semiconductor radiation damage such as rate effects (flux), incident energy, and device temperature have not yet been fully examined. Moreover, the available data are from a very small sampling of detectors (sometimes a single device) and do not, in general, cover the complete fluence range of interest.

Despite these shortcomings, several interesting features emerge from the existing data. The most apparent is that HgI₂ appears to be relatively immune to proton and neutron-induced radiation damage. No resolution degradation was found from intermediate energy protons at fluences up to 10^{12} p/cm². Similarly, no degradation was found from high-energy protons although the effects of fluences significantly beyond 10^8 p/cm² have not been investigated and accordingly the suitability of HgI₂ for long-term space mission remains in question. Additionally, the material is apparently not susceptible to damage from intermediate energy neutrons.

The situation for cadmium telluride is less clear. No data were found for effects of high-energy protons although the results at intermediate energy suggest vulnerability beginning in the region of 10^8 p/cm². Neutron data are also incomplete although at intermediate energies (8 MeV) the damage threshold for resolution degradation is relatively high (10^{10} n/cm²). While no evidence of activation was reported, effects similar to those in CZT can be expected.

The radiation susceptibility of CZT is also in question. There is evidence of resolution degradation from 200 MeV protons beginning in the region of 10^9 p/cm² as well as a downward shift in peak channel proportional to the proton fluence. However, the resolution degradation was apparent only in a 3 mm thick device and not a 2 mm detector. There is also evidence that the resolution degradation is dependent on bias conditions although this is based on the results from a single detector. Detector response changes following high-energy proton irradiation are consistent with increased electron trapping and the associated decreases in the mobility-lifetime product. With intermediate energy protons (1.3 MeV), bulk and interstrip leakage was evident but only at high fluence levels. Damage for moderated fission neutrons is evident only after 10^{10} n/cm². Neutron activation lines from cadmium and tellurium isotopes appear after about 10^{10} n/cm². It is interesting to note that annealing at room temperature was very effective in restoring resolution losses. Resolution degradation and the downward trend in peak position from 5 MeV α particles, while based on single detector, are generally consistent with proton data.

References

1. G. T. Ewan, *Nuclear Instruments and Methods*, 162, 75, 1979.
2. R. H. Pehl, N. W. Madden, J. H. Elliott, T. W. Raudorf, R. C. Tramell, and L. S. Darken, *IEEE Transactions on Nuclear Science*, NS-26, No. 1, p. 321, 1979.
3. J. S. Iwanczyk, Y. J. Young, J. G. Bradley, J. M. Conley, A. L. Albee, and T. E. Economov, *IEEE Transactions on Nuclear Science*, Vol. 36, No. 1, p. 841, 1989.
4. F. D. Becchetti, R. S. Raymond, R. A. Ristinen, W. F. Schepple, and C. Ortale, *Nuclear Instruments and Methods*, 213, p. 127, 1983.
6. B. E. Patt, R. C. Dolin, T. M. Devore, J. M. Markakis, J. S. Iwanczyk, N. Dorri, and J. Trombka, *Nuclear Instruments and Methods*, A 299, p. 176, 1990.
5. G. H. Nakano, W. L. Imhof, and J. R. Kilner, *IEEE Transactions Nuclear Science*, Vol. NS-23, No. 1, p. 468, 1976.
7. R. A. Ristinen, R. J. Petersen, J. J. Hamill, F. D. Becchetti, and G. Entine, *Nuclear Instruments and Methods*, 188, p. 445, 1981.
8. T. Shoji, T. Taguchi, Y. Hiratate, and Y. Inuishi, *IEEE Transactions on Nuclear Science*, Vol. NS-26, No. 1, p. 316, 1979.
10. L. S. Varnell, W. A. Mohone, E. L. Hull, J. F. Butler, A. S. Wong, *SPIE Technical Conference Proceedings*, Denver, Colorado, Vol. 2806, 1996.
9. L. M. Bartlett, NASA Goddard Space Flight Center, Greenbelt, Maryland, private communication.
11. L. M. Bartlett, C. M. Stahle, P. Shu, L. M. Barber, S. D. Barthelmy, N. Gehrels, J. F. Krizmanic, P. Kurczynski, D. Palmer, A. Parsons, B. J. Teegarden, and T. Tueller, *SPIE Technical Conference Proceedings*, Denver, Colorado, Vol. 2859, 1996.

Figures and Captions:

Figure 1. Pulse height spectrum of 5 MeV alpha obtained from a small irradiated area. The alpha flux is $2.8 \times 10^7 \alpha/\text{cm}^2\text{-s}$.

Figure 2. Peak position and full wide at half maximum as a function of exposure time for α irradiated CZT detector.

Figure 3. Alpha particle response map of detector surface as measured by deviations in counts in the photopeak channel. Dark areas indicate non-responsive regions.