CONTRACT TITLE AND NUMBER:

Development of a Catalyst for Conversion
of Syngas-Derived Materials to Isobutylene
DE-AC22-91PC90042

Date:

Quarterly Report No. 12

Reporting Period:

1/1/94-3/31/94

Contractor:

UOP

50 E. Algonquin Rd.

Des Plaines, IL 60017-5016

Author:

Paul T. Barger

Contract Period: March 15, 1991 to September 14, 1995

QUARTERLY TECHNICAL REPORT

The goals of this project are to develop a catalyst and process for the conversion of syngas to isobutanol. The research will identify and optimize key catalyst and process characteristics. In addition, the commercial potential of the new process will be evaluated by an economic analysis. This report describes pilot plant testing using a 10/1 methanol/ethanol feed blend to identify potential catalysts for the conversion of lower alcohols derived from synthesis gas to isobutanol and other C₄₊ oxygenates.

The previous work in this project found that a typical Cu/Zn/Al oxide methanol synthesis catalyst is capable of producing isobutanol and isobutryaldehyde from a feed consisting of a blend of methanol and ethanol¹. Best performance was obtained at moderate temperature (300 °C) and low pressure (30 psig). This report describes the results of space velocity testing with this catalyst to elucidate the reaction pathway. It has been found that at high ethanol conversion levels (low space velocities), yields of isobutanol and other C₄₊ oxygenates do not increase with increasing methanol conversion. This suggests that Cu/Zn/Al oxide is not active for the condensation of methanol alone to higher alcohols. Therefore, new catalyst formulations are being evaluated for this reaction using the Cu/Zn/Al oxide performance as a baseline. Promising materials will also be examined at high ethanol conversion levels and with a methanol only feed to determine their capability to condense methanol.

Catalyst screening has focussed in two directions. Materials related to conventional methanol synthesis catalysts and Pd on a Zn/Mn/Zr oxide have been evaluated. The former materials have included a low Cu-content Cu/Zn/Al oxide, a Cu/Zn/Mn oxide and two Zn/Al oxides. The Cu containing materials are less active than the baseline Cu/Zn/Al catalyst, but give better selectivities and productivities to the desired products. However, comparison of the performances of these materials to that of the baseline catalyst at a lower temperature, where conversion is comparable, show similar productivities. The non-Cu containing samples have substantially lower activity and selectivity to the desired higher oxygenates.

CLEARED BY
PATENT COUNSEL

MASTER

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Catalysts consisting of Pd (0, 0.2, 2%) on a Zn/Mn/Zr oxide support have been found to be active for the conversion of methanol/ethanol to C₄ oxygenates. These catalysts, particularly with 2% Pd, have shown the best selectivities and productivities to date. Future work will pursue the use of this type of catalyst for this process, including effect of catalyst composition (support and metal function) and space velocity tests to probe the reaction pathway.

EXPERIMENTAL

Catalysts

Mixed metal oxide catalysts consisting of Cu/Zn/Al oxides (31/42/27 and 11/63/26 molar) were prepared by co-precipitating aqueous solutions of nitrate salts with sodium carbonate at 50 °C and pH 7. After extensive water washing, the precipitates were dried at 110 °C for 12 hours, sized to 20-40 mesh and calcined at 400 °C in air for 2 hours. Cu/Zn/Mn oxide (34/33/33 molar) and Zn/Al oxide (74/26 and 63/37 molar) catalysts were prepared by a similar co-precipitation method.

A Zr/Zn/Mn oxide (33/33/33 molar) support was prepared by co-precipitating an aqueous solution of nitrate salts with potassium hydroxide at 50 °C and pH 11². The solid was washed with H₂O, dried at 127 °C for 15 hours, sized to 20-40 mesh and calcined at 327 °C in air for 3 hours. Samples of the Zr/Zn/Mn oxide were impregnated with an aqueous PdCl₂ solution and re-calcined at 400 °C to afford a final catalysts with 0.2 and 2.1 wt.% Pd.

Catalytic Testing Procedure

The pilot plant testing of catalysts for the conversion of methanol/ethanol blend to isoalcohols was accomplished as follows. The catalyst, as 20-40 mesh granules, was loaded into a 1/2" I.D. stainless steel reactor. The reactor was first N₂ purged at 250 °C, 10 psig, 0.5 scf/hr for 1 hour then pressure tested with N₂ at 250 °C, 500 psig for 1 hour. After restarting the N₂ purge, temperature and pressure were adjusted to the desired conditions. After 2 hours, the methanol/ethanol blend (10/1 molar) was cut into the plant at the desired rate and continued for 16 hours. Product analyses were obtained using two on-line GCs to analyze the total hydrocarbon/oxygenate product and the overhead gas. Conversions, selectivities and productivities (including CO and CO₂) are based on moles of carbon. For all of the tests described in this report, the averages of results obtained between 8 and 16 hours on stream are reported.

A listing of the pilot plant runs included in this report, as well as the methanol/ethanol runs using methanol synthesis type catalysts described in Quarterly Report 11¹, is given in Table 1.

RESULTS AND DISCUSSION

Reaction Pathway for Cu/Zn/Al Oxide Catalyst in the Conversion of Methanol/Ethanol to Isoalcohols

Previous work in this project identified conditions at which a conventional Cu/Zn/Al oxide methanol synthesis catalyst catalyzes the conversion of a methanol/ethanol feed to isobutanol and other C_4 oxygenates¹. The best performance, in terms of selectivity and productivity, was obtained at 300 °C and 30 psig (Table 2). It was also found, using a different catalyst, that the condensation step is greatly favored by the use of low pressure. This suggests that aldehyde intermediates, formed by the dehydrogenation of the alcohols, may be important in this reaction.

One of the primary mechanistic questions in the production of branched C_4 oxygenates from methanol is the relative rates of the C_1 - C_1 , C_1 - $C_{2,3}$ and C_2 - C_2 condensation steps. The aldol condensation between two C_2 species is expected to yield straight chain C_4 products. The fact that the observed C_4 oxygenate products are highly branched, even with ethanol in the feed, suggests that their formation occurs by sequential C_1 aldol condensations to C_2 and C_3 intermediates. This indicates that C_1 - $C_{2,3}$ coupling is substantially favored over C_2 - C_2 condensation. In view of the dehydrogenation equilibrium constants at 327 °C of 0.03 for methanol $\rightleftharpoons$ formaldehyde + H_2 and 1.12 for ethanol $\rightleftharpoons$ acetaldehyde + H_2 , it appears that branched C_4 s compounds are formed by the condensation of methanol with acetaldehyde and propionaldehyde.

In order to determine whether C_1 - C_1 coupling occurs over the Cu/Zn/Al oxide catalyst, a series of low space velocity tests with high ethanol conversion have been conducted. The extent of C_1 - C_1 coupling can be elucidated by comparing of the yields of isobutanol and total C_{4+} oxygenates at these conditions with the yields at lower ethanol conversions. Figures 1 and 2 show feed conversions and product yields versus 1/space velocity at 300 °C, 30 psig. At space times greater than 0.5 hr, ethanol conversion exceeds 90%, while methanol and total carbon conversions increase from about 70% to near 90%. However, Figure 2 shows that in this space time region isobutanol and total C_{4+} oxygenates yields are essentially flat. Only CO yield shows an increase comparable to the total carbon conversion rise. This indicates that the additional conversion occurring in this portion of the catalyst bed is due to methanol reforming to CO rather than aldol condensation. Therefore, it appears that Cu/Zn/Al oxide material is a poor catalyst for the C_1 - C_1 condensation required for the production of higher oxygenates from methanol alone. Based on these results, the research effort in this project has focussed on identifying alternative catalysts for this reaction. The performance of the Cu/Zn/Al oxide catalyst will be used as a baseline for judging the results obtained with new materials.

Screening of Catalysts for the Conversion of Methanol/Ethanol to Isoalcohols

Several mixed metal oxide compositions that are related to low temperature and high temperature methanol synthesis catalysts have been evaluated in the methanol/ethanol conversion screening test. The results of these runs are summarized in Table 2. Low Cu content Cu/Zn/Al oxide and Cu/Zn/Mn oxide catalysts are less active than the baseline catalyst, but have superior selectivity and productivity to the desired C₄ oxygenates at 350 °C. However, comparison of the performances of these materials with that of the baseline catalyst at 300 °C, where conversions are comparable, show similar productivities. It is also unlikely that these materials would be significantly more active for the C₁-C₁ coupling needed for methanol only conversion than the baseline catalyst. Zn/Cr and Zn/Al mixed metal oxide materials, based on high temperature methanol synthesis catalysts, show substantially lower activity and productivity of the desired higher alcohol products.

Catalysts consisting of Pd impregnated on a Zn/Mn/Zr mixed metal oxide prepared by co-precipitation of metal nitrates with KOH have been described as having high selectivity for isobutanol from synthesis gas². However, severe conditions (high temperatures and very high pressures) are required to achieve attractive conversion levels. One interpretation of these results is that this catalyst is active for the condensation of light alcohols to higher alcohols with high selectivity to isobutanol, but requires severe conditions for CO hydrogenation. If this is the case, these materials would be promising catalysts for a methanol to higher alcohols process. Therefore, we have evaluated a representative material, with and without noble metal, in the methanol/ethanol screening test. Table 3 summarizes the testing results obtained with a Zn/Mn/Zr metal oxide with 0, 0.2 and 2 wt.% Pd added by impregnation with a PdCl₂ solution. These materials show lower activity than the baseline catalyst, but significantly higher selectivity to isobutanol, isobutraldehyde and total C₄₊ oxygenates. In spite of the lower conversions, the Pd containing catalyst give higher productivities to the desired products than the baseline catalyst. In fact, the productivities observed with the 2% Pd catalyst are the highest obtained to date in this program. Future work will pursue the use of this type of catalyst for this process, including effect of catalyst composition (support and metal function) and space velocity tests to probe the reaction pathway.

CONCLUSIONS

Space velocity testing has been used to show that the reaction pathway for condensation of a methanol/ethanol feed blend to higher alcohols over typical Cu/Zn/Al oxide methanol synthesis catalyst proceeds primarily through C₁-C_{2,3} coupling with little C₁-C₁ coupling. This suggests that Cu/Zn/Al oxide would not be active for the condensation of methanol alone to higher alcohols. Therefore, new catalyst formulations are being evaluated for this reaction using the Cu/Zn/Al oxide performance as a baseline. Promising materials will also be examined at high ethanol conversion levels and with a methanol only feed to determine their capability to condense methanol.

Materials related to conventional methanol synthesis catalysts and Pd on a Zn/Mn/Zr oxide have been evaluated for the conversion of methanol/ethanol to isobutanol. The former materials have shown performances either comparable or inferior to the baseline Cu/Zn/Al oxide catalyst. Catalysts consisting of Pd (0, 0.2, 2%) on a Zn/Mn/Zr oxide support have been found to be active for the conversion of methanol/ethanol to C₄ oxygenates. The 2% Pd sample has given the best selectivities and productivities to date. Future work will pursue the use of this type of catalyst for this process, including effect of catalyst composition (support and metal function) and space velocity tests to probe the reaction pathway.

REFERENCES

- 1) P. T. Barger, DOE Quarterly Report No. 11, (1994).
- 2) W. Keim and W. Falter, Catalysis Letters 3, 59, (1989);
M. Roper, W. Keim and J. Seibring, Eur. Pat. Appl. 208,012, (1986);
W. Falter and W. Keim, Eur. Pat. Appl. 335,092, (1989).

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Table 1. Run List

RUN	CATALYST		CATALYST DESCRIPTION	SIZE	LOADING g	CONDITIONS				
	A Book #	B Book #				TEMP (C) INLET MAX	TOTAL PSIG	MeOH WHSV	FEED RATIO MeOH/EtOH/Inert	
176	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
177	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	5	300	30	2	1/0.1/2 N2	
178	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	5	250	30	2	1/0.1/2 N2	
179	7923-18A		Zn/Cr (75/25) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
180	7923-69		Cu/Zn/Mn (34/33/33) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
181	7887-37		Zn/Al (74/26) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
182	7887-39		Cu/Zn/Al (11/63/26) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
183	7887-41		Zn/Al (63/37) Oxide (Lab PPT)	20-40M	5	350	30	2	1/0.1/2 N2	
184	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	10	250	30	1	1/0.1/2 N2	
185	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	5	250	75	2	1/0.1/2 N2	
186	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	2.5	300	30	4	1/0.1/2 N2	
187	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	10	300	30	1	1/0.1/2 N2	
188	7923-55		Zr/Zn/Mn (34/34/32) Oxide	20-40M	5	350	30	2	1/0.1/2 N2	
189	7923-62		0.2%Pd / Zn/Mn/Zr (34/34/32) Oxide	20-40M	5	350	30	2	1/0.1/2 N2	
190	7923-64		2.1%Pd / Zn/Mn/Zr (34/34/32) Oxide	20-40M	5	350	30	2	1/0.1/2 N2	
191	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	5	300	30	2	1/0.1/2 N2	
192	7923-85		Cu/Zn/Al (31/42/27) Oxide (Lab PPT)	20-40M	1.75	300	30	5.7	1/0.1/2 N2	

Table 2. Evaluation of Methanol Synthesis Type Catalysts

Run	176	177	179	182	180	181	183
Catalyst	Cu/Zn/Al Oxide (31/42/27)		Zn/Cr Oxide (75/25)	Cu/Zn/Al Oxide (11/63/26)	Cu/Zn/Mn Oxide (34/33/33)	Zn/Al Oxide (74/26)	Zn/Al Oxide (63/37)
Temperature (°C)	350	300	350	350	350	350	350
Conversion (%)							
MeOH	97.6	67.3	14.9	62.3	50.8	15.5	17.7
EtOH	99.2	95.9	31.5	97.9	88.8	72.8	81.2
Selectivities (mole%)							
iC ₄ OH	2.0	5.8	2.8	7.5	5.5	1.1	2.0
iC ₄ Ald	2.2	2.3	0.4	6.0	7.2	0.2	0.2
Total C ₄₊ Oxy	5.9	12.7	6.2	21.4	14.6	9.8	8.9
CO	45.5	33.0	7.5	28.9	19.4	1.8	2.0
CO ₂	40.8	37.9	30.4	31.7	42.0	16.2	18.4
Productivities (mole/kg cat/hr)							
iC ₄ OH	1.4	3.0	0.7	3.7	2.3	0.2	0.4
Total C ₄₊ Oxy	4.1	6.6	1.5	8.1	6.0	1.8	1.8

Conditions: 30 psig, 2 hr⁻¹ MeOH WHSV, 1/0.1/2 MeOH/EtOH/N₂

Table 3. Evaluation of Pd on Zn/Mn/Zr Oxide Catalysts

Run	176	177	188	189	190
Catalyst	Cu/Zn/Al Oxide (31/42/27)		Zn/Mn/Zr Oxide (34/34/32)	0.2%Pd on Zn/Mn/Zr Oxide (34/34/32)	2.1%Pd on Zn/Mn/Zr Oxide (34/34/32)
Temperature (°C)	350	300	350	350	350
Conversion (%)					
MeOH	97.6	67.3	8.6	30.3	47.9
EtOH	99.2	95.9	49.5	87.5	97.4
Selectivities (mole%)					
iC ₄ OH	2.0	5.8	12.9	7.6	10.3
iC ₄ Ald	2.2	2.3	0.2	7.4	10.4
Total C ₄₊ Oxy	5.9	12.7	18.1	20.8	25.0
CO	45.5	33.0	0.0	9.1	14.7
CO ₂	40.8	37.9	14.3	26.0	28.2
Productivities (mole/kg cat/hr)					
iC ₄ OH	1.4	3.0	0.7	2.2	4.3
Total C ₄₊ Oxy	4.1	6.6	1.5	6.0	10.4

Conditions: 30 psig, 2 hr⁻¹ MeOH WHSV, 1/0.1/2 MeOH/EtOH/N₂

Figure 1.

Cu/Zn/Al Performance vs. Space Time Methanol/Ethanol to Higher Alcohols

Figure 2.

Cu/Zn/Al Performance vs. Space Time Methanol/Ethanol to Higher Alcohols