DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

CONF-950402--6
FINAL

TECHNOLOGY DEVELOPMENT FOR COBALT F-T CATALYSTS

Contract No. DE-AC22-92PC92108

TOPICAL REPORT No. 3

ZIRCONIA PROMOTION OF FISCHER-TROPSCH COBALT CATALYSTS: BEHAVIOR IN FIXED-BED AND SLURRY BUBBLE COLUMN REACTORS

Prepared for
Energy International Corporation
135 William Pitt Way
Pittsburgh, PA 15238

under Contract with the
U.S. Department of Energy
Pittsburgh, PA 15236

By

Rachid Oukaci, George Marcelin, and James G. Goodwin, Jr.
University of Pittsburgh
Chemical & Petroleum Engineering Department
Pittsburgh, PA 15261

(Submitted to ACS National Meeting in Anaheim, CA, April 1995)

January 17, 1995

RECEIVED
USDOE/PETC
95 MAR -3 AM 10:12
ACQUISITION & ASSISTANCE DIV.

MASTER

CLEARED BY
PATENT COUNSEL

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

85

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ABSTRACT

A series of cobalt-based F-T catalysts supported on alumina and silica were prepared with different loadings of Zr and different sequences of impregnation of Co and Zr. All catalysts were extensively characterized by different methods. The catalysts were evaluated in terms of their activity and selectivity both in fixed bed and slurry bubble column reactors. Addition of ZrO_2 to both Co/SiO_2 and $\text{Co/Al}_2\text{O}_3$ catalysts resulted in at least a twofold increase in the catalyst activity for F-T synthesis in the fixed bed reactor. In the slurry bubble column reactor, a similar promotion effect was observed for the SiO_2 -supported catalysts, while the addition of Zr to a cobalt/alumina catalyst had a less significant effect.

INTRODUCTION

Cobalt-based catalysts have been widely used for Fischer-Tropsch (F-T) synthesis since the early part of the century because of their high activity and high selectivity for long chain paraffins (1-8). Various promoters, such as the alkali series or some rare earth oxides have been often used to improve the cobalt metal activity for F-T synthesis or its selectivity for higher hydrocarbons. While several studies of F-T synthesis over ZrO_2 -supported Co (1,9), Ni (9), Ni/Co (9), and Pd (10) have been reported in the literature, very little is known about the use of ZrO_2 as a promoter on other supports. When ZrO_2 was used as the support, it has been found to increase the selectivity for higher hydrocarbons. In recent years, Shell filed a number of patents (11-13) for the development of Co-based F-T catalysts containing ZrO_2 as a promoter. Addition of up to 15 wt% ZrO_2 promotor was found to increase the overall activity of the Co catalyst without affecting the selectivity for higher hydrocarbons.

A series of cobalt-based F-T catalysts supported on alumina and silica were prepared with different loadings of Zr and different sequences of impregnation of Co and Zr in order to investigate the role of ZrO_2 on affecting the F-T reaction in both fixed bed and slurry bubble column reactors.

EXPERIMENTAL

All catalysts compared in this study consisted of 20 wt% cobalt and different amounts of zirconia (up to 15 wt% Zr), the support being alumina (Vista B) or silica (Davison 952). The supports were all calcined at 500°C for 10 hours prior to their impregnation with the metal solutions. They were impregnated in one or two steps with aqueous solutions of cobalt nitrate and/or zirconium nitrate. In the case of $[\text{Co}/8.5\text{Zr}(\text{O})]/\text{SiO}_2$, a solution of zirconium tetra-n-propoxide in a mixture of n-propanol, toluene, and acetyl acetone was used to impregnate the Zr in the initial impregnation step. In the case of single step impregnations and in the initial step of some of the sequentially impregnated SiO_2 -supported catalysts, the aqueous metal precursor solution-support mixture was kneaded for 3.5 hours (11-13). Incipient wetness impregnation was used for the subsequent addition of Zr (11-13) and in all the steps for the other sequentially

impregnated SiO_2 -catalysts and all the alumina-supported catalysts. The catalysts were dried at 115°C and calcined in air at 300°C for 2 hours after each impregnation step. The catalysts are listed in Table 1 with the corresponding preparation methods.

Prior to H_2 chemisorption or reaction, the catalysts were reduced in H_2 at 250°C for the SiO_2 -supported catalysts and 350°C for the Al_2O_3 -supported catalysts, for 10 hours following a $1^\circ\text{C}/\text{min}$ ramp. They have all been extensively characterized by different methods, including elemental analysis, BET physisorption, particle size distribution, X-ray diffraction, hydrogen chemisorption, temperature programmed reduction. Table 2 summarizes the relevant characterization data.

The catalysts were evaluated in terms of their activity and selectivity both in a fixed bed reactor and in a slurry bubble column reactor. Typically, 0.15 to 0.35 g of prereduced catalyst were charged into the fixed bed reactor tube and rereduced overnight at 300°C . The reaction was carried out at 220°C , 1 atm, a H_2/CO ratio of 2.0, and a total flow rate of $90\text{ cm}^3/\text{min}$. No inert diluent was used. Sample analyses were taken after approximately 2, 5, 9, and 24 hours on-stream. In some cases the temperature was varied between 210 and 240°C in order to calculate an Arrhenius activation energy. Product analysis for C1 to C20 hydrocarbons was performed by on-line gas chromatography. CO conversion rates were calculated based on the GC analysis of the products. Anderson-Schultz-Flory (A-S-F) distributions were plotted and the chain growth probability, α , calculated using the C4 to C16 data.

For the slurry bubble column tests, the catalyst was first reduced *ex-situ* in a fluidized bed assembly and then transferred into a glove box having an inert atmosphere for weighing and subsequent transfer into the slurry bubble column reactor. Approximately 15 g of catalyst and 200 g of liquid medium were used in a run. Typically, the reaction was carried out at 240°C , a total pressure of 450 psi, a H_2/CO ratio of 2, and with 60% N_2 diluent. Analysis of the gas products, CO, CO_2 and C1 to C5, was performed hourly. Liquid products were collected at the end of each 24 hour period, blended, and submitted for analysis. A-S-F plots of the liquid products were used to determine α . After reaching steady-state under these conditions, temperature, pressure, and H_2/CO ratio were varied in turn to study the effect of process conditions. A typical complete run lasted about 10 days. Only the base Co catalysts (non-promoted Co/SiO_2 and $\text{Co}/\text{Al}_2\text{O}_3$) and the most active catalysts in the fixed bed reactor were tested in the slurry bubble column reactor.

RESULTS AND DISCUSSION

From XRD measurements, it was found that the average diameter of the Co oxide crystallites for all catalysts varied within a narrow range (ca. 20-30 nm), regardless of the amount of Zr present or the support used. In addition, the XRD results suggest that Zr was highly dispersed on Co/SiO_2 since no Zr compound phases were detected.

The TPR results show little difference in the degree of reduction for all the catalysts with the exception of $[\text{0.7Zr}+\text{Co}]/\text{SiO}_2$ and $[\text{Co}/8.5\text{Zr}]/\text{Al}_2\text{O}_3$, which exhibited the lowest and the highest

reducibility, respectively. The Al_2O_3 -supported catalysts had in general higher reducibilities than their silica-supported analogs. It was also found that all the catalysts used in this study were reduced to the maximum degree (defined as % Co reduced during TPR to 900°C) during the standard reduction procedure at 250°C .

The sequentially-impregnated $\text{Zr}/\text{Co}/\text{SiO}_2$ catalysts showed an increase in the amount of total hydrogen chemisorbed compared to that for $[\text{Co}]/\text{SiO}_2$. On the other hand, for the sequentially-impregnated $\text{Co}/\text{Zr}/\text{SiO}_2$ catalysts, the Zr addition did not influence significantly the amount of H_2 -chemisorption. The co-impregnated catalyst $[\text{8.5Zr}+\text{Co}]/\text{SiO}_2$ had almost twice as much H_2 uptake as either $[\text{0.7Zr}+\text{Co}]/\text{SiO}_2$ or $[\text{Co}]/\text{SiO}_2$. The opposite effect was observed with the Al_2O_3 -supported catalysts. The sequentially-impregnated $\text{Co}/\text{Zr}/\text{Al}_2\text{O}_3$ catalyst and the co-impregnated catalyst with low Zr loading $[\text{1.4Zr}+\text{Co}]/\text{Al}_2\text{O}_3$ had the highest H_2 uptakes.

Table 3 shows selected data obtained from fixed bed reaction which indicate the effect of ZrO_2 promotion on F-T activity and selectivity. While the alumina-supported Co catalysts were found to be in general more active than their silica-supported analogs, Zr promotion of both Co/SiO_2 and $\text{Co}/\text{Al}_2\text{O}_3$ increased significantly the overall rate of F-T synthesis, compared to the non-promoted catalysts. In addition, the promoting effect of ZrO_2 was more significant on the alumina-supported catalysts, especially the sequentially impregnated catalyst $[\text{Co}/\text{8.5Zr}]/\text{Al}_2\text{O}_3$. The method of preparation and the amount of promoter used also affected the catalyst activity and selectivity. The sequentially impregnated $[\text{Co}/\text{Zr}]$ catalysts appeared to be the most active. Addition of Zr beyond 8.5 wt% for the SiO_2 -supported catalysts did not seem to have any beneficial effect. The catalysts with the highest Zr loadings (wt% $\text{Zr} > 1.4$) had the highest values of α compared to the non-promoted catalysts, even though the CH_4 selectivity was also slightly higher in several cases. On the other hand, small amounts of Zr promotion (wt% $\text{Zr} = 0.7$ or 1.4) appeared to have a slightly negative effect on the values of α .

Table 4 shows selected data obtained at 240°C , 450 psi, and H_2/CO ratio of 2, in the slurry bubble column reactor for catalysts consisting of Co supported on silica and alumina, respectively. As in the case of the fixed bed testing, the ZrO_2 promoter was found to influence the overall activity of both the silica- and alumina-supported catalysts. However, while the alumina-supported Co catalysts were also found to be in general more active than their silica-supported analogs, the promoting effect of ZrO_2 was not as significant on the alumina-supported catalysts. Diffusion limitations in the liquid medium in the slurry bubble column reactor may be invoked to explain the discrepancies in the results obtained in the two reaction systems. The overall rate observed for the catalyst $[\text{Co}/\text{8.5Zr}]/\text{Al}_2\text{O}_3$ was high, but most probably diffusion limited.

In summary, ZrO_2 appears to be an excellent rate promoter for SiO_2 - and Al_2O_3 -supported Co catalysts. Addition of Zr in both catalysts, probably hinders the formation of Co aluminates and Co silicates, either during the preparation and pretreatment or during the F-T synthesis reaction itself. In addition, high levels of promotion act to increase the selectivity for higher hydrocarbons.

REFERENCES

1. Withers, H. P., Jr., and Eliezer, K. F., and Mitchell, J. W., *Ind. Eng. Chem. Res.* **29**, 1807 (1990).
2. Brady, R. C., and Pettit, R., *J. Am. Chem. Soc.* **103**, 1287 (1981).
3. Reuel, R. C., and Bartholomew, C. H., *J. Catal.* **85**, 78 (1984).
4. Reuel, R. C., and Bartholomew, C. H., *J. Catal.* **85**, 63 (1984).
5. Foley, H. C., and Hong, A. J., *Appl. Catal.* **61**, 351 (1990).
6. Rathousky, J., Zukal, A., Lapidus A., and Krylova, A., *Appl. Catal.* **79**, 167 (1991).
7. Iglesia, E., Soled, S. L., and Fiato, R. A., *J. Catal.* **137**, 212 (1992).
8. Iglesia, E., Soled, S. L., Fiato, R. A., and Grayson, H., *J. Catal.* **143**, 345 (1993).
9. Bruce, L. A., Hope, G. J., and Mathews, J. F., *Appl. Catal.* **8**, 349 (1983).
10. Alekseev, O. S., Zaikovskii, V. I., and Ryndin, Yu. I., *Appl. Catal.* **63**, 37 (1990).
11. Hoek, A., Joustra, A. H., Minderhoud, J. K., and Post, M. F., *UK Pat. Appl. GB 2 125 062 A* (1983).
12. Hoek, A., Minderhoud, J. K., and Post, M. F. M., *Lednor, P. W. Eur. Pat. Appl. EP 110 449 A1* (1984).
13. Post, M. F. M. B., and Sie, S. T. B., *Eur. Pat. Appl. 0 167 215 A2* (1985).

Table 1: Catalyst Preparation Methods Used

Catalyst ^a	Step # 1 ^b		Step # 2 ^b	
	Method	Solution	Method ^a	Solution
[Co]/SiO ₂	Kneading	aqueous(Co)	N/A	N/A
[0.7Zr/Co]/SiO ₂	Kneading	aqueous(Co)	Inc. Wet.	aqueous(Zr)
[1.4Zr/Co]/SiO ₂	Kneading	aqueous(Co)	Inc. Wet.	aqueous(Zr)
[8.5Zr/Co]/SiO ₂	Kneading	aqueous(Co)	Inc. Wet.	aqueous(Zr)
[Co/4.0Zr]/SiO ₂	Inc. Wet.	aqueous(Zr)	Inc. Wet.	aqueous(Co)
[Co/8.5Zr(O)]/SiO ₂	Inc. Wet.	organic(Zr)	Inc. Wet.	aqueous(Co)
[Co/8.5Zr]/SiO ₂	Inc. Wet.	aqueous(Zr)	Inc. Wet.	aqueous(Co)
[Co/15.0Zr]/SiO ₂	Inc. Wet.	aqueous(Zr)	Inc. Wet.	aqueous(Co)
[0.7Zr+Co]/SiO ₂	Kneading	aqueous(Co+Zr)	N/A	N/A
[8.5Zr+Co]/SiO ₂	Kneading	aqueous(Co+Zr)	N/A	N/A
[Co]/Al ₂ O ₃	Inc. Wet.	aqueous(Co)	N/A	N/A
[1.4Zr+Co]/Al ₂ O ₃	Inc. Wet.	aqueous(Co+Zr)	N/A	N/A
[8.5Zr+Co]/Al ₂ O ₃	Inc. Wet.	aqueous(Co+Zr)	N/A	N/A
[8.5Zr/Co]/Al ₂ O ₃	Inc. Wet.	aqueous(Co)	Inc. Wet.	aqueous(Zr)
[Co/8.5Zr]/Al ₂ O ₃	Inc. Wet.	aqueous(Zr)	Inc. Wet.	aqueous(Co)

(a) Nomenclature: [A/xxB] or [xxA/B] = "A" Impregnated after "B"; [A+xxB] = Co-Impregnated "A" and "B"; B(O) = Organic Compound of B used instead of Nitrate (Nonaqueous Impregnating Solution); xx = wt% Zr

(b) Catalysts Dried for 5 hrs at 115 °C and Calcined for 2 hrs at 300°C after Each Step.

Table 2: Catalyst Characterization Results

Catalyst	H ₂ Chemisorption		TPR	XRD
	Total (μmol H ₂ /g cat)	% Co Dispersion	% Reduct. (25-900°C)	Co ₃ O ₄ d _p (nm)
[Co]/SiO ₂	82	4.8	75	27
[0.7Zr/Co]/SiO ₂	141	8.3	80	28
[1.4Zr/Co]/SiO ₂	149	8.8	81	27
[8.5Zr/Co]/SiO ₂	122	7.2	81	29
[Co/8.5Zr(O)]/SiO ₂	87	5.1	75	31
[Co/8.5Zr]/SiO ₂	93	5.5	75	27
[0.7Zr+Co]/SiO ₂	67	4.0	64	20
[8.5Zr+Co]/SiO ₂	125	7.3	77	24
[Co]/Al ₂ O ₃	48	2.8	85	20
[1.4Zr+Co]/Al ₂ O ₃	71	4.2	82	19
[8.5Zr+Co]/Al ₂ O ₃	55	3.2	85	26
[8.5Zr/Co]/Al ₂ O ₃	43	2.5	79	24
[Co/8.5Zr]/Al ₂ O ₃	114	6.7	96	22

Table 3: Fixed Bed Reaction Results

Catalyst	ACTIVITY		SELECTIVITY	
	% CO Conversion	Rate (g CH ₂ /g cat/hr)	CH ₄ (wt%)	α
[Co]/SiO ₂	2.9	0.094	22.4	0.61
[0.7Zr/Co]/SiO ₂	3.8	0.121	26.7	0.55
[1.4Zr/Co]/SiO ₂	3.8	0.123	28.3	0.56
[8.5Zr/Co]/SiO ₂	3.9	0.125	28.9	0.67
[Co/4.0Zr]/SiO ₂	2.6	0.161	22.2	0.73
[Co/8.5Zr(O)]/SiO ₂	5.7	0.182	28.7	0.62
[Co/8.5Zr]/SiO ₂	5.0	0.160	23.5	0.63
[Co/15.0Zr]/SiO ₂	3.1	0.179	22.7	0.73
[0.7Zr+Co]/SiO ₂	3.6	0.114	28.0	0.56
[8.5Zr+Co]/SiO ₂	4.6	0.147	22.0	0.69
[Co]/Al ₂ O ₃	3.3	0.077	28.4	0.62
[8.5Zr+Co]/Al ₂ O ₃	3.3	0.183	22.0	0.70
[8.5Zr/Co]/Al ₂ O ₃	1.3	0.073	24.1	0.67
[Co/8.5Zr]/Al ₂ O ₃	5.0	0.275	24.0	0.67

P = 1 atm, T = 220°C, H₂/CO = 2, Catalyst Weight = 0.15-0.35 g, Total Flow Rate = ca. 90 cm³/min, Time-On-Stream = ca. 25 hrs

Table 4: Slurry Bubble Column Reaction Results

Catalyst	ACTIVITY		SELECTIVITY	
	% CO Conversion	Rate (g CH ₂ /g cat/hr)	CH ₄ (wt%)	α
[Co]/SiO ₂	14.3	0.67	7.6	0.83
[Co/8.5Zr(O)]/SiO ₂	25.5	1.21	8.6	0.84
[Co/8.5Zr]/SiO ₂	26.6	1.24	10.7	0.82
[Co/15.0Zr]/SiO ₂	20.9	0.93	6.7	0.83
[0.7Zr+Co]/SiO ₂	23.2	1.08	9.4	0.82
[8.5Zr+Co]/SiO ₂	24.8	1.18	8.5	0.84
[Co]/Al ₂ O ₃	27.1	1.34	7.9	0.82
[1.4Zr+Co]/Al ₂ O ₃	30.9	1.41	12.1	0.83
[Co/8.5Zr]/Al ₂ O ₃	27.5	1.54	10.4	0.84

Catalyst Weight: 13-17g, T = 240°C, P = 450 psi, H₂/CO Ratio = 2, Total Flow Rate = ca.15 L/min, or 3 cm/sec Linear Velocity, Diluent: N₂: ca. 60%, Time-On-Stream = ca. 35 hrs.