DISTRIBUTION SHEET

To Distribution	From LLW Disposal Program	Page 1 of 1
Project Title/Work Order		Date Feb. 8, 1995
		EDT No. N/A
		ECN No. 610857

Name	MSIN	Text With All Attach.	Text Only	Attach./ Appendix Only	EDT/ECN Only
C. T. Kincaid	K9-33				
J. W. Shade	H5-27				X
K. C. Burgard	G6-13				X
G. F. Williamson	G6-13				X
J. A. Voogd	G6-13				X
J. M. Conner	H5-27				X
M. G. Piepho	H0-36				X
F. Mann	H0-36				X
R. J. Murkowski	G6-13				X
Central Files	L8-04	X			
OSTI (2)	L8-07	X			

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

RECEIVED

MAR 22 1995

OSTI

DE

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ENGINEERING CHANGE NOTICE

Page 1 of 81. ECN 610857Proj.
ECN

2. ECN Category (mark one) Supplemental ☐ Direct Revision ☒ Change ECN ☐ Temporary ☐ Standby ☐ Supersedeure ☐ Cancel/Void ☐	3. Originator's Name, Organization, MSIN, and Telephone No. J. W. Shade, TWRS Disposal Technology, H5-27, 373-5922	3a. USQ Required? ☐ Yes ☒ No	4. Date February 7, 1995
	5. Project Title/No./Work Order No. N/A	6. Bldg./Sys./Fac. No. N/A	7. Approval Designator N/A
	8. Document Numbers Changed by this ECN (includes sheet no. and rev.) N/A	9. Related ECN No(s). N/A	10. Related PO No. N/A
	11a. Modification Work ☐ Yes (fill out Blk. 11b) ☒ No (NA Blks. 11b, 11c, 11d)	11b. Work Package No. N/A	11c. Modification Work Complete N/A Cog. Engineer Signature & Date
12. Description of Change Direct revision of WHC-SD-WM-EE-004, Rev. 0. Changes are noted in pages 3 through 8 of this ECN.			
13a. Justification (mark one) Criteria Change ☐ Design Improvement ☐ Environmental ☐ Facility Deactivation ☐ As-Found ☐ Facilitate Const ☐ Const. Error/Omission ☐ Design Error/Omission ☒			
13b. Justification Details Rev. 1 corrects minor errors discovered in the original document and adds Appendix which contains correspondence with the DOE-HQ Performance Assessment Peer Review Panel.			
14. Distribution (include name, MSIN, and no. of copies) attached		RELEASE STAMP OFFICIAL RELEASE 38 BY WHC DATE FEB 27 1995 Sta. 21	

A-7900-013-3 (11/94) GEF096

WHC-SD-WM-EE-004, Rev. 1

Errata for

Kincaid et al. October 1993, *Performance Assessment of Grouted
Double-Shell Tank Waste Disposal at Hanford*
(WHC-SD-WM-EE-004, Rev. 0)

The following changes are reflected in Rev. 1 of the subject document. The pages listed here are based on the Rev. 0 edition.

Page	Position	Correction
2.42	Table 2.2	Change heading over the 3rd column to read "Hanford Airborne Effluents"
		Change 3rd line of 1st column to read "Percent of Limit or Standard"; delete "%" at end
		Change 4th line of 1st column to read "Percent of Natural Background Radiation"; delete "%" at end
2.46	Footnote (a)	Append the following: "An updated copy of Appendix E that incorporates the minor change now appears in Appendix R."
2.55/2.56	Table 2.4	Add footnote (i) to row titled " ^{239/240} Pu": "The radionuclide pair ^{239/240} Pu is difficult to distinguish and, therefore, is shown as a lumped pair. The activity shown is total for the pair. The half life is for ²³⁹ Pu, the isotope with the longer half life."
2.56	Table 2.4	Footnote (h): Change "Activity shown is total for pair" to "Activity shown is total for the parent."
3.2	Figure 3.1	Change text block under the heading "Release" from "Diffusion Release" to "Advection and Diffusion Release"
3.18	1st full paragraph	Change 1st sentence to read, "This scenario . . . domestic use and irrigation of crops . . ."
3.20	Section 3.2.4.5, 2nd paragraph	Append the following text to the end of the paragraph, "Radionuclide concentrations on the ground surface are based on the radionuclide concentrations in the waste feed stream rather than the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with adding dry materials to form the grout."

Page	Position	Correction
	Section 3.2.4.5, 3rd paragraph, 4th line	Append to the end of the sentence the following text, ". . .to a depth of 15 cm."
	Section 3.2.4.5, 3rd paragraph	Append the following text to the end of the paragraph, "Radionuclide concentrations mixed into the 15-cm-thick contaminated surface layer are based on radionuclide concentrations in the waste feed stream rather than in the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with the addition of dry materials to form the grout."
3.65	3rd line	Change "No ₂ " to "NO ₂ "
3.78	1st paragraph, 3rd line	Delete "(superimposed on the recharge map; see Figure 3.14)"
3.80	Table 3.20	The column heading (6th column) that begins "Travel Time" should read as follows: <div style="text-align: center;"> Travel Time <u>100-m Well (days)</u> <u>River (years)</u> </div> The last entry in this table (row reads "R=5 cm/yr and Q _w =45 m ³ /d"; column reads "Well Intercept Factor") contains a typographical error. The value 0.0105 should be 0.105.
3.80	Text following Eq. (3.9)	Following the sentence ending "... approximately 90,000 m ² " insert the following sentence: "For the 5-cm/yr recharge rate cases, the 0.245-m ³ /d factor in Eq (3.9) is replaced by 12.3-m ³ /d."
3.81	Text following Eq. (3.10)	Insert "Eq. (3.10) applies to the 0.1-cm/yr infiltration rate cases. For the 5-cm/yr recharge rate cases, the 0.245-m ³ /d factor in Eq. (3.10) is replaced by 12.3-m ³ /d."
3.82	1st paragraph, 4th line	Replace "ananisotropic" with "an anisotropic"

Page	Position	Correction
3.96	Section 3.5.5.1, 2nd paragraph, 1st line	Insert "(Napier et al. 1988)" after the words "GENII environmental dosimetry software system."
3.97	Last line before section 3.6	Change the acronym from "(NAMP)" to "(VAMP)."
3.105	Section 3.6.2.2, 1st full paragraph, 10th line	Change "conservate" to "conservative"
3.123	Figure 3.21	Change the figure text identifying the area between the "Asphalt Barrier" and "Concrete Roof" from "Low Conductivity Concrete Cells" to "Low Hydraulic Conductivity Computational Cells"
3.124 to 3.128	Table 3.42	Change last row in table from "Crack Site. ." to "Crack Size. ." Change text in last row, below column reading "Construction Joint Cracks in Concrete Walls" from "Full Mode. ." to "Full Node. ."
3.130	Section 3.6.3.2, 1st paragraph	Change ". . .5,000 years for concrete and 5,150 years for the asphalt barrier. . ." to ". . .5,000 years for the asphalt barrier and 5,150 years for the concrete. . ."
3.131	Section 3.6.4.1, 2nd paragraph, 2nd to last sentence	Amend the sentence to end as follows: ". . .radon-222 was estimated assuming an emanating power of 100%."
3.139	Table 3.45, 2nd to last line	Change "9,467 cm/s" to "3.00 x 10 ⁻² cm/s"
3.143	Table 3.46, Case 2.6A, last sentence	Change "3-ft" to "91.4-cm"
3.147	Section 3.6.5.5, last paragraph, 5th line	Capitalize the first word of the sentence beginning "the relative uncertainties. . ."

Page	Position	Correction
4.11	1st full paragraph, 6th line in parenthesis	Change "grout 3C" to "group 3C"
4.12	Table 4.2	<p>Change heading reading "Cumulative Dose in Person-rem/yr" to "Cumulative Dose (person-rem/yr)"</p> <p>Add footnote [footnote (e)] to row labeled "Community Well" that reads, "The community well serves 80 people."</p> <p>Add footnote [footnote (f)] to row labeled "River" that reads, "The downstream population in the river scenario is 5×10^6 people."</p>
4.17	1st full paragraph, 1st line	The end of the line of text should read ". . the dose from drinking. ."
4.23 and 4.24	Tables 4.4 and 4.5	<p>Add footnote [footnote (a)] that reads "Supplementary tables showing the results of the full inventory analysis are included in Appendix P, Section P.7." The tables include results for the intruder dose calculations of both the drilling intrusion scenario (Table 4.4) and the post-drilling residential scenario (Table 4.5). These tables include the following information:</p> <ul style="list-style-type: none"> - Grout Inventory - Driller Scenario Pathway Dose Factors - Driller Scenario Dose (mrem/yr, % of total dose) - Post-Driller Garden Scenario Pathway Dose Factors - Post-Driller Scenario Dose (mrem/yr, % of total dose)
4.26	Section 4.1.4.2, last line on page	Change to read: "Technetium-99 and tin-126 account for 96% . . ."
4.50	Section 4.2.3, 1st paragraph, 5th line	Insert the following sentence immediately after the sentence ending with ". . .and selenium-79": "Detailed results of the dosimetry sensitivity analysis are presented in Appendix N."
4.52	Last paragraph, 2nd sentence	Change position of the word "only": "In both the drilling and post-drilling habitation scenarios, only changes in Cs-137 are important at 100 years."

Page	Position	Correction
4.57	Section 4.3.6, 4th line	Replace the words ". . .dose factors for..." at the end of the line with ". . .consumption rate of. . ."
6.7	Bio for Rhoads	Change "Health Physics Department" to "Health Risk Assessment Department"
		Change the end of the first sentence in the text to read ". . . (1985-1988), Health Physics Department (1988-1993), and Health Risk Assessment Department (1993-present)."
6.8	Bio for Snyder	Change "Health Physics Department" to "Health Risk Assessment Department"
Chapter 7 - References		Chapter 7 has been revised to include references missing from the Rev. 0 document. Throughout the text, reference callouts have been corrected where necessary.
I.1	1st paragraph	Change second sentence: "GENII (GENeration II), the second generation of Hanford Environmental Dosimetry System computer codes, was originally. . ."
I.4	1st paragraph	Change reference of last sentence from "Section I.1" to "Section I.4".
I.5	1st paragraph	Change "Snyder et al. 1992" to "Snyder et al. 1994."
I.17	Exhibit I.3, footnote (a)	Change "Pci" to "pCi"
I.23	Snyder et al. reference	Change to most recent version: "Snyder, S.F., W. T. Farris, B.A. Napier, T.A. Ikenberry, and R.O. Gilbert. 1994. <i>Parameters Used in the Environmental Pathways and Radiological Dose Modules (DESCARTES, CIDER, and CRD Codes) of the Hanford Environmental Dose Reconstruction Integrated Codes (HEDRIC)</i> . PNWD-2023 HEDR Rev. 1, Battelle, Pacific Northwest Laboratories, Richland, Washington.
M.2	Exhibit M.1	Add footnote by the "X" in the column labeled "Flood, Upward Diffusion,. . ." and the row labeled "Drinking water from: groundwater". The new footnote reads: "This pathway was not considered in the flood and upward diffusion scenarios."

WHC-SD-WM-EE-004, Rev. 1

Page	Position	Correction
M.6	Column title in Exhibit M.3	Replace the "/" with a space in the column heading "Post-drilling/Home Garden Scenario Parameters (units)".
M.6	Table references	Make the reference format consistent in the "Basis" column. [Should be NAME (19xx)]
M.7	4th paragraph, last sentence	Remove "/" in last sentence reading "post-drilling/home garden scenario"
P.54	New section P.7	Add new Section P.7 providing supplementary tables showing the inventory, dose factors, and percent of total dose for the full inventory analysis of the intruder dose calculations for both the drilling intrusion scenario and the post-drilling residential scenario. These supplementary tables are labeled Tables P.12 through P.16. The existing Section P.7 becomes Section P.8.
-	Appendix R	Add the new Appendix R, "Compilation of Responses to Requests for Further Information Made by the Peer Review Panel"

RELEASE AUTHORIZATION

**Document
Number:**

WHC-SD-WM-EE-004 Rev. 1, Vol. ~~1~~

**Document
Title:**

Performance Assessment of Grouted Double-Shell Tank
Waste Disposal at Hanford

Release Date:

February 13, 1995

**This document was reviewed following the
procedures described in WHC-CM-3-4 and is:**

APPROVED FOR PUBLIC RELEASE

WHC Information Release Administration Specialist:

V.L. Birkland
V.L. Birkland

February 13, 1995

TRADEMARK DISCLAIMER. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors.

This report has been reproduced from the best available copy. Available in paper copy and microfiche. Printed in the United States of America. Available to the U.S. Department of Energy and its contractors from:

U.S. Department of Energy
Office of Scientific and Technical Information (OSTI)
P.O. Box 62
Oak Ridge, TN 37831
Telephone: (615) 576-8401

Available to the public from:

U.S. Department of Commerce
National Technical Information Service (NTIS)
5285 Port Royal Road
Springfield, VA 22161
Telephone: (703) 487-4650

SUPPORTING DOCUMENT		1. Total Pages 1194
2. Title Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford	3. Number WHC-SD-WM-EE-004	4. Rev No. 1
5. Key Words grout, performance assessment	6. Author Name: J. W. Shade (WHC lead) <i>J. W. Shade</i> 2/10/95 Signature Organization/Charge Code 73300/D46BD	
7. Abstract This document assesses the performance of the Grout Disposal Facility after closure. The facility and disposal environment are modeled to predict the long-term impacts of the disposal action. The document concludes that the disposal system provides reasonable assurance that doses to the public will remain within the performance objectives. This document is required by DOC Order 5820.2A.		
		8. RELEASE STAMP OFFICIAL RELEASE 38 BY WHC DATE FEB 27 1995 <i>Sta. 21</i>

RECORD OF REVISION		(1) Document Number WHC-SD-WM-EE-004		Page
(2) Title Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford				
CHANGE CONTROL RECORD				
(3) Revision	(4) Description of Change - Replace, Add, and Delete Pages	Authorized for Release		
		(5) Cog. Engr.	(6) Cog. Mgr.	Date
1 RS	(7) Complete revision of Rev. 0. Complete errata sheet included in ECN.	K. C. Burgard	<i>[Signature]</i>	2/7/95

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PERFORMANCE ASSESSMENT OF GROUTED DOUBLE-SHELL TANK WASTE DISPOSAL AT HANFORD

Compiled by: C. T. Kincaid^(a)
J. W. Shade^(b)
G. A. Whyatt^(a)
M. G. Piepho^(b)
K. Rhoads^(a)

J. A. Voogd^(b)
J. H. Westsik, Jr.^(a)
M. D. Freshley^(a)
K. A. Blanchard^(a)
B. G. Lauzon^(b)

September 1994

A Westinghouse Hanford Company Report
Prepared by
Pacific Northwest Laboratory and
Westinghouse Hanford Company
for the U.S. Department of Energy

UG DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

-
- (a) Pacific Northwest Laboratory
 - (b) Westinghouse Hanford Company

Errata for
Kincaid et al. October 1993, *Performance Assessment of Grouted
Double-Shell Tank Waste Disposal at Hanford*
(WHC-SD-WM-EE-004, Rev. 0)

The following changes are reflected in Rev. 1 of the subject document. The pages listed here are based on the Rev. 0 edition.

Page	Position	Correction
2.42	Table 2.2	Change heading over the 3rd column to read "Hanford Airborne Effluents" Change 3rd line of 1st column to read "Percent of Limit or Standard"; delete "%" at end Change 4th line of 1st column to read "Percent of Natural Background Radiation"; delete "%" at end
2.46	Footnote (a)	Append the following: "An updated copy of Appendix E that incorporates the minor change now appears in Appendix R."
2.55/2.56	Table 2.4	Add footnote (i) to row titled " ^{239/240} Pu": "The radionuclide pair ^{239/240} Pu is difficult to distinguish and, therefore, is shown as a lumped pair. The activity shown is total for the pair. The half life is for ²³⁹ Pu, the isotope with the longer half life."
2.56	Table 2.4	Footnote (h): Change "Activity shown is total for pair" to "Activity shown is total for the parent."
3.2	Figure 3.1	Change text block under the heading "Release" from "Diffusion Release" to "Advection and Diffusion Release"
3.18	1st full paragraph	Change 1st sentence to read, "This scenario . . . domestic use and irrigation of crops . . ."
3.20	Section 3.2.4.5, 2nd paragraph	Append the following text to the end of the paragraph, "Radionuclide concentrations on the ground surface are based on the radionuclide concentrations in the waste feed stream rather than the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with adding dry materials to form the grout."

Page	Position	Correction
	Section 3.2.4.5, 3rd paragraph, 4th line	Append to the end of the sentence the following text, "...to a depth of 15 cm."
	Section 3.2.4.5, 3rd paragraph	Append the following text to the end of the paragraph, "Radionuclide concentrations mixed into the 15-cm-thick contaminated surface layer are based on radionuclide concentrations in the waste feed stream rather than in the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with the addition of dry materials to form the grout."
3.65	3rd line	Change "No ₂ " to "NO ₂ "
3.78	1st paragraph, 3rd line	Delete "(superimposed on the recharge map; see Figure 3.14)"
3.80	Table 3.20	The column heading (6th column) that begins "Travel Time" should read as follows: <div style="text-align: center;"> Travel Time <u>100-m Well (days) River (years)</u> </div> The last entry in this table (row reads "R=5 cm/yr and Q _w =45 m ³ /d"; column reads "Well Intercept Factor") contains a typographical error. The value 0.0105 should be 0.105.
3.80	Text following Eq. (3.9)	Following the sentence ending "... approximately 90,000 m ² " insert the following sentence: "For the 5-cm/yr recharge rate cases, the 0.245-m ³ /d factor in Eq (3.9) is replaced by 12.3-m ³ /d."
3.81	Text following Eq. (3.10)	Insert "Eq. (3.10) applies to the 0.1-cm/yr infiltration rate cases. For the 5-cm/yr recharge rate cases, the 0.245-m ³ /d factor in Eq. (3.10) is replaced by 12.3-m ³ /d."
3.82	1st paragraph, 4th line	Replace "anaisotropic" with "an anisotropic"

Page	Position	Correction
3.96	Section 3.5.5.1, 2nd paragraph, 1st line	Insert "(Napier et al. 1988)" after the words "GENII environmental dosimetry software system."
3.97	Last line before section 3.6	Change the acronym from "(NAMP)" to "(VAMP)."
3.105	Section 3.6.2.2, 1st full paragraph, 10th line	Change "conservate" to "conservative"
3.123	Figure 3.21	Change the figure text identifying the area between the "Asphalt Barrier" and "Concrete Roof" from "Low Conductivity Concrete Cells" to "Low Hydraulic Conductivity Computational Cells"
3.124 to 3.128	Table 3.42	Change last row in table from "Crack Site. ." to "Crack Size. ." Change text in last row, below column reading "Construction Joint Cracks in Concrete Walls" from "Full Mode. ." to "Full Node. ."
3.130	Section 3.6.3.2, 1st paragraph	Change ". . .5,000 years for concrete and 5,150 years for the asphalt barrier. . ." to ". . .5,000 years for the asphalt barrier and 5,150 years for the concrete. . ."
3.131	Section 3.6.4.1, 2nd paragraph, 2nd to last sentence	Amend the sentence to end as follows: ". . .radon-222 was estimated assuming an emanating power of 100%."
3.139	Table 3.45, 2nd to last line	Change "9,467 cm/s" to " 3.00×10^{-2} cm/s"
3.143	Table 3.46, Case 2.6A, last sentence	Change "3-ft" to "91.4-cm"
3.147	Section 3.6.5.5, last paragraph, 5th line	Capitalize the first word of the sentence beginning "the relative uncertainties. . ."

Page	Position	Correction
4.11	1st full paragraph, 6th line in parenthesis	Change "grout 3C" to "group 3C"
4.12	Table 4.2	<p>Change heading reading "Cumulative Dose in Person-rem/yr" to "Cumulative Dose (person-rem/yr)"</p> <p>Add footnote [footnote (e)] to row labeled "Community Well" that reads, "The community well serves 80 people."</p> <p>Add footnote [footnote (f)] to row labeled "River" that reads, "The downstream population in the river scenario is 5×10^6 people."</p>
4.17	1st full paragraph, 1st line	The end of the line of text should read ". . the dose from drinking. ."
4.23 and 4.24	Tables 4.4 and 4.5	<p>Add footnote [footnote (a)] that reads "Supplementary tables showing the results of the full inventory analysis are included in Appendix P, Section P.7." The tables include results for the intruder dose calculations of both the drilling intrusion scenario (Table 4.4) and the post-drilling residential scenario (Table 4.5). These tables include the following information:</p> <ul style="list-style-type: none"> - Grout Inventory - Driller Scenario Pathway Dose Factors - Driller Scenario Dose (mrem/yr, % of total dose) - Post-Driller Garden Scenario Pathway Dose Factors - Post-Driller Scenario Dose (mrem/yr, % of total dose)
4.26	Section 4.1.4.2, last line on page	Change to read: "Technetium-99 and tin-126 account for 96% . . ."
4.50	Section 4.2.3, 1st paragraph, 5th line	Insert the following sentence immediately after the sentence ending with ". . .and selenium-79": "Detailed results of the dosimetry sensitivity analysis are presented in Appendix N."
4.52	Last paragraph, 2nd sentence	Change position of the word "only": "In both the drilling and post-drilling habitation scenarios, only changes in Cs-137 are important at 100 years."

Page	Position	Correction
4.57	Section 4.3.6, 4th line	Replace the words ". . .dose factors for..." at the end of the line with ". . .consumption rate of. . ."
6.7	Bio for Rhoads	Change "Health Physics Department" to "Health Risk Assessment Department" Change the end of the first sentence in the text to read ". . . (1985-1988), Health Physics Department (1988-1993), and Health Risk Assessment Department (1993-present)."
6.8	Bio for Snyder	Change "Health Physics Department" to "Health Risk Assessment Department"
Chapter 7 - References		Chapter 7 has been revised to include references missing from the Rev. 0 document. Throughout the text, reference callouts have been corrected where necessary.
I.1	1st paragraph	Change second sentence: "GENII (GENeration II), the second generation of Hanford Environmental Dosimetry System computer codes, was originally. . ."
I.4	1st paragraph	Change reference of last sentence from "Section I.1" to "Section I.4".
I.5	1st paragraph	Change "Snyder et al. 1992" to "Snyder et al. 1994."
I.17	Exhibit I.3, footnote (a)	Change "Pci" to "pCi"
I.23	Snyder et al. reference	Change to most recent version: "Snyder, S.F., W. T. Farris, B.A. Napier, T.A. Ikenberry, and R.O. Gilbert. 1994. <i>Parameters Used in the Environmental Pathways and Radiological Dose Modules (DESCARTES, CIDER, and CRD Codes) of the Hanford Environmental Dose Reconstruction Integrated Codes (HEDRIC)</i> . PNWD-2023 HEDR Rev. 1, Battelle, Pacific Northwest Laboratories, Richland, Washington.
M.2	Exhibit M.1	Add footnote by the "X" in the column labeled "Flood, Upward Diffusion,. . ." and the row labeled "Drinking water from: groundwater". The new footnote reads: "This pathway was not considered in the flood and upward diffusion scenarios."

WHC-SD-WM-EE-004, Rev. 1

Page	Position	Correction
M.6	Column title in Exhibit M.3	Replace the "/" with a space in the column heading "Post-drilling/Home Garden Scenario Parameters (units)".
M.6	Table references	Make the reference format consistent in the "Basis" column. [Should be NAME (19xx)]
M.7	4th paragraph, last sentence	Remove "/" in last sentence reading "post-drilling/home garden scenario"
P.54	New section P.7	Add new Section P.7 providing supplementary tables showing the inventory, dose factors, and percent of total dose for the full inventory analysis of the intruder dose calculations for both the drilling intrusion scenario and the post-drilling residential scenario. These supplementary tables are labeled Tables P.12 through P.16. The existing Section P.7 becomes Section P.8.
-	Appendix R	Add the new Appendix R, "Compilation of Responses to Requests for Further Information Made by the Peer Review Panel"

Summary

The Hanford Defense Waste Environmental Impact Statement (HDWEIS) (U.S. DOE 1987) and the subsequent Record of Decision established that the low-level fraction of the liquid, radioactive wastes stored in double-shell tanks at the Hanford Site will be treated to produce a grout waste form that immobilizes the wastes. The grouted waste will then be disposed of in large, subsurface concrete vaults on the 200 Area plateau. U.S. Department of Energy (DOE) Order 5820.2A (U.S. DOE 1988a) requires that

"Field organizations with disposal sites shall prepare and maintain a site-specific radiological performance assessment for the disposal of waste for the purpose of demonstrating compliance with the performance objectives ..."

This document provides the performance assessment required for the Grout Disposal Facility. It provides a technical analysis of potential impacts to the public from the release of waste radionuclides disposed in grout. This analysis includes an evaluation of disposal system properties, environmental conditions, and public exposure scenarios. These potential future conditions are analyzed for time periods extending up to 10,000 years for comparison to the performance objectives. Analyses beyond 10,000 years are conducted to evaluate potential maximum impact. Although future events cannot be predicted with certainty, the range of scenarios presented in this performance assessment provides some understanding of the critical elements influencing public exposure from waste disposal.

This performance assessment is intended by DOE order to be a living document, meaning that, as needed, the analyses will be updated to provide a new assessment of impacts. Concurrently, this performance assessment provides information that enables the disposal program to develop and implement improvements to the waste disposal system.

S.1 Disposal System

The Grout Disposal Facility is located within the Hanford Site, in southeastern Washington state, approximately 205 m (675 ft) above mean sea level (Figure S.1). This area, considered to be a semiarid desert, receives an average of 16 cm (6 in.) of precipitation per year. The soil column at the disposal site consists of sand, silts, and gravel deposits that extend approximately 60 to 70 m (200 to 230 ft) from the surface to the uppermost groundwater aquifer.

Approximately 120 million liters (32 million gallons) of low-level liquid waste from the Hanford Site's double-shell tanks will be disposed of as grouted waste in the Grout Disposal Facility. Liquid wastes from the tanks will be mixed with cementitious dry materials, and the resulting grout slurry will be

S9211085.51

Figure S.1. Map of the Hanford Site and the Grout Disposal Facility

pumped into large concrete vaults to solidify. Each vault will contain up to 5.3 million liters (1.4 million gallons) of grouted waste derived from 3.8 million liters (1 million gallons) of waste. The remaining space between the top of the radioactive grout and the interior roof of the vaults will be filled with a non-radioactive grout to prevent subsidence.

The Grout Disposal Facility uses many engineered barriers to isolate the grouted wastes from the environment. Figure S.2 shows a cross section through a typical pair of vaults and shows the major components of the engineered disposal system. The grout provides the initial immobilization of the wastes. Because the waste contains hazardous waste components, the vaults containing the grout are designed to meet Resource Conservation and Recovery Act (RCRA) requirements for double containment. The vaults have a double liner and a leachate collection and detection system. Each vault is surrounded by a 1-m (3.3-ft) thick solid asphalt pavement diffusion barrier to retard water migration into, and contaminant movement out of, the vaults. The RCRA cover consisting of a sloped clay/soil layer will be placed over each pair of vaults. The Grout Disposal Facility eventually will be covered with an additional protective barrier and marker system that is currently under development at the Hanford Site. This protective barrier is intended to reduce water infiltration and to warn and deter inadvertent intruders.

Figure S.2. Grout Disposal Facility--Closed Vault Pair

S.2 Regulatory Guidance/Performance Objectives

DOE Order 5820.2A provides performance objectives for the disposal of low-level radioactive wastes. The DOE Richland Operations Office (RL) has also issued an order designated DOE-RL Order 5820.2A that provides additional guidance on performance objectives specific to the Hanford Site. These performance objectives focus on protection of the 1) general public, 2) inadvertent intruders, and 3) groundwater resources. In this performance assessment, performance objectives from DOE orders are called regulatory performance objectives. In addition, the Hanford Grout Disposal Program has established further programmatic performance objectives. These performance objectives are presented below and are summarized in Table S.1.

S.2.1 General Public Protection

The regulatory performance objective (from DOE-RL Order 5820.2A) for the protection of the general public is to ensure that the maximum exposure to any member of the public does not exceed 25 mrem/yr for at least 1,000 years after disposal. Exposures occurring after 1,000 years are to be as low as reasonably achievable (ALARA) such that the maximum population exposure is less than 500 person-rem/yr. The programmatic performance objective is to not exceed 25 mrem/yr for 10,000 years and ALARA thereafter. In addition, federal clean air regulations limit releases of radon to the atmosphere to a rate less than 20 pCi/m²-s.

S.2.2 Inadvertent Intruder Protection

DOE Order 5820.2A provides performance objectives for protection of intruders who may inadvertently intrude into the facility after loss of active institutional control (100 years). The Order provides a limit of 100 mrem/yr for continuous exposure and 500 mrem for a single acute exposure. The DOE-RL Order 5820.2A specifies that for wastes that may exceed performance objectives for intruders beyond 100 years, passive controls are to be included in the disposal system to warn and deter intruders for up to 500 years.

S.2.3 Groundwater Resource Protection

DOE Order 5820.2A requires protection of the groundwater resource consistent with federal, state, and local requirements. DOE-RL 5820.2A clarifies that dose from radionuclides in the groundwater should not exceed an effective dose equivalent of 4 mrem/yr to an individual who drinks 2 L/d (2.1 qt/d) from the aquifer. Although the DOE-RL Order specifies these objectives must be met for at least 1,000 years, the grout program has adopted 10,000 years as a programmatic performance objective for meeting the dose limit. Both radionuclide and chemical impacts are presented to demonstrate groundwater resource protection.

Table S.1. Performance Objectives for Grout Disposal System

Exposure Pathway	Time Period	Performance Objective
<i>General Public Protection</i>		
Maximum individual dose through all pathways	≤1,000 yr (DOE-RL 5820.2A) ≤10,000 yr (Programmatic)	25 mrem/yr
General population protection (ALARA)	>1,000 yr (DOE-RL 5820.2A) >10,000 yr (Programmatic)	500 person-rem/yr
Air emissions after disposal (radon)		20 pCi/m ² -s
<i>Intruder Protection</i>		
Continuous radiation exposure to intruder	≥500 yr (DOE-RL 5820.2A)	100 mrem/yr
Single acute radiation exposure to intruder	≥500 yr (DOE-RL 5820.2A)	500 mrem
<i>Groundwater Resource Protection</i>		
Drinking water	≤1,000 yr (DOE-RL 5820.2A) ≤10,000 yr (Programmatic)	4 mrem/yr

S.3 Exposure Scenarios

The engineered Grout Disposal System is designed to effectively contain the radioactive wastes for hundreds to thousands of years and beyond. Short and intermediate half-life radionuclides will decay to benign products before reaching the environment. As the engineered system degrades over time, long-half-life radionuclides and chemicals eventually will be released into the environment. The contaminants reach the accessible environment by the natural processes of diffusion and advection through the engineered disposal system and down through the surrounding soils and sediments. Eventually the contaminants reach the groundwater and the Columbia River. Members of the public may be exposed to the contaminants by using the groundwater or Columbia River water, through exposure to contaminated soil, or from gaseous releases. Humans who inadvertently intrude into the disposal site will also be exposed to the contaminants.

In this performance assessment, computer models were used to predict the movement of radionuclides through the engineered disposal system, down through the unsaturated soils and sediments beneath the grout vaults, and into the groundwater and Columbia River. Several scenarios were then evaluated to estimate the potential dose to individuals exposed to the radionuclides. These scenarios include a farm or garden irrigated with water drawn from the groundwater, use of the groundwater as a drinking source, and use of the Columbia River water. Scenarios were also examined to estimate the acute and chronic impacts of human intrusion into a grout vault.

In the irrigated farm scenario, water drawn from a well downgradient of the Grout Disposal Facility is used for irrigation, livestock water, and drinking water on a 2-hectare (5-acre) farm. The maximally exposed individual receives radiation dose by drinking the well water, consuming crops and animal products, and contacting the contaminated soil.

The irrigated garden scenario is similar to the irrigated farm scenario except that it excludes the animal product pathway. A lower volume of water is used in the garden scenario than in the farm scenario. The garden scenario is used to assess the impacts from potentially higher contaminant concentrations in groundwater resulting from reduced groundwater pumping.

In the Columbia River scenario, groundwater transports contaminants to the Columbia River. A population of 5 million people living along or near the Columbia River is assumed to use the river for irrigation, livestock water, drinking water, fishing, and recreation. The total dose to all affected users is calculated for this scenario, rather than a dose to a maximum individual.

Two scenarios are used to estimate the acute and chronic impacts of human intrusion into the disposal site. The acute intrusion scenario considers inadvertent drilling directly through the grouted waste. Radiation exposure occurs from contacting the drill tailings and inhaling suspended dust during drilling. The chronic intrusion scenario considers the impacts to an individual who inhabits the site after drilling. Contaminated soil is spread around the homesite. Exposure occurs by consuming food grown at the site and directly contacting the soil.

S.4 Methodology

This performance assessment was conducted through a series of computer simulations to model the long-term performance of the Grout Disposal Facility. The simulations were used to follow the movement of contaminants from the grout, through the vault and asphalt barrier, and through the soils and sediments to the groundwater beneath the disposal site. Specific simulations or cases were run to compare to performance objectives (compliance cases), to evaluate design features (design cases), and to evaluate model sensitivities (sensitivity cases).

Four compliance cases were run to provide the basis for comparison to the performance objectives outlined in Section S.2. These cases incorporate different models for the long-term performance of the

disposal system. All included the gradual degradation over time of the grout, vault, and asphalt barrier from cracking and biodegradation of the asphalt. The compliance cases included a central compliance case and cases with delayed cracking of the vault and asphalt, reduced structure resolution, and a composite model of cracking.

The five design cases help determine the role of individual components in the engineered system and identify those that most significantly influence the long-term exposure and dose estimates. This knowledge provides insights into the value of the disposal system components and defines those system components whose physical, hydraulic, and transport properties are important to the system. The design cases evaluated the roles of the grout waste form, vault, asphalt barrier, gravel layer above the asphalt barrier, and the RCRA cover.

Sensitivity cases were developed to evaluate how sensitive model estimates were to changes in input parameters and to understand the effect of inherent material properties on the overall system performance. These properties include contaminant retardation coefficients, unsaturated hydraulic properties, saturated hydraulic properties, degradation rates, and degradation locations. The sensitivity cases also considered the impacts of a higher water infiltration rate. Ranges of these properties are modeled to quantify the impact on public exposure. The relative change in dose resulting from property changes is a measure of the sensitivity.

S.5 Performance Assessment Results

Several key points should be considered when interpreting the performance assessment results.

1. A person living in the Columbia Basin currently receives approximately 300 mrem/yr of background radiation from natural sources (sun, food, soil). The calculated doses defined within this report are in addition to the naturally occurring background radiation.
2. The calculated doses show the incremental impact of the grout disposal action.
3. The radiation doses described for the irrigated farm and garden, drinking water, and intrusion scenarios are for a maximally exposed individual.
4. The values provided here are indicators only of the disposal system's performance. The uncertainties associated with any long-term projection necessitate judgment and careful consideration when interpreting the projected values.

As described earlier, the performance objectives focus on protection of 1) the general public, 2) inadvertent intruders, and 3) the groundwater resource. Each objective is addressed below.

S.5.1 General Public Protection

Exposures to the public are postulated to occur through the use of groundwater for farming and gardening or through use of the Columbia River. Table S.2 shows the results of the analyses. The dose to the maximally exposed individual is estimated to be less than 25 mrem/yr for times up to 1,000 and 10,000 years after disposal. Beyond 10,000 years, the estimated doses are above 25 mrem/yr. However, the 500-person-rem/yr performance objective is the applicable objective at these times. Collective doses for comparison to ALARA are shown at the time of peak exposure. All performance objectives related to protection of the general public, as defined in DOE Order 5820.2A and DOE-RL Order 5820.2A, are met by the planned disposal of grouted low-level waste.

Figure S.3 shows the estimated farm scenario doses for the compliance cases. The modeling indicates that dose to an exposed individual is derived primarily from the long-lived radionuclides iodine-129, technetium-99, and neptunium-237. Releases to the environment via groundwater are projected to be extremely low for several thousand years. After this period, iodine-129 and technetium-99 are the greatest contributors to any projected dose. After 100,000 years, the rate of iodine-129 and technetium-99 release to the aquifer decreases because of the depletion of the inventory. Neptunium-237 concentrations begin to show in the groundwater at this time. The long half life of each of these species (greater than 10,000 years) contributes to the species' persistence at or near the disposal site. The sorption coefficients in the soil column and grout and the slow rate of aquifer recharge contributes to the sustained contamination over long time periods.

Table S.2. Comparison to Performance Objectives for Protection of the General Public

Exposure Path	Performance Objective	Maximum Estimated Dose or Concentration (through 1,000 years)	Maximum Estimated Dose or Concentration (through 10,000 years)
Groundwater, irrigated farm	25 mrem/yr	<0.01 mrem/yr	5.2 mrem/yr
Groundwater, irrigated garden	25 mrem/yr	<0.01 mrem/yr	8.2 mrem/yr
Radon emission in air	20 pCi/m ² -s	N/A	8 pCi/m ² -s
Columbia River	ALARA - 500 person rem/yr	N/A	<0.1 person-rem/yr
Groundwater, community well	ALARA - 500 person rem/yr	N/A	2.8 person-rem/yr

Figure S.3. Estimated Farm Scenario Doses for the Compliance Cases. Shaded areas indicate where performance objectives would not be met.

S.5.2 Inadvertent Intruder Protection

DOE orders specify that for wastes remaining hazardous to intruders beyond 100 years, passive controls are to be included in the disposal system to deter intruders for up to 500 years. Because the grouted waste will contain concentrations of radionuclides that may exceed the performance objectives after the 100-year active institutional control period, passive controls are being designed into the disposal system to warn and deter potential inadvertent intruders. The grout will be disposed at a minimum depth of 5 m below grade. In addition, the disposal site will include markers such as granite monoliths at the site boundary plus several layers of discs emplaced above the waste zone to warn of the potential hazard. The large rock layer in the Hanford barrier, the asphalt barrier, and reinforced-concrete vault all act to deter intrusion for at least 500 years. Therefore, the dose impacts for the intruder scenarios are compared to the performance objectives at 500 years in Table S.3.

The intruder doses at 500 years are within the performance objectives. Based on the analysis performed for the intruder scenarios, there is reasonable assurance that the doses to inadvertent intruders will be within the performance objectives of 500 mrem for acute exposure and 100 mrem/yr for chronic exposure at 500 years.

Table S.3. Comparison to Intruder Protection Performance Objective

Scenario	Dose at 500 Years	Performance Objective
Drilling	8.4 mrem ^(a)	500 mrem
Post-Drilling Habitation	72 mrem/yr	100 mrem/yr

(a) Effective Dose Equivalent.

S.5.3 Groundwater Resource Protection

Table S.4 shows the results of the groundwater resource protection analyses. Both radionuclide and chemical (nitrates) impacts are shown. The regulatory performance objectives identified in DOE-RL Order 5820.2A for groundwater resource protection at 1,000 years are met by the grouted waste disposal action. The longer term, 10,000-year programmatic performance objective is achieved by all but one compliance case evaluated in this performance assessment. In that one case, there is sudden drainage from the vault roof associated with the degradation of the roof. This drainage is not observed in the other compliance cases because those cases more realistically include drainage paths associated with the cover block joints. At the time of maximum impact beyond 10,000 years, doses from drinking groundwater are above 4 mrem/yr, peaking at 19 to 26 mrem/yr at about 50,000 years.

Table S.4. Comparison to Groundwater Protection Performance Objective

	Performance Objective	Maximum Estimated Dose or Concentration at 1,000 Years	Maximum Estimated Dose or Concentration at 10,000 Years
Radionuclides	4 mrem/yr	<10 ⁻⁵ mrem/yr	0.4 to 6.9 mrem/yr
Nitrates (as N)	NA ^(a)	<10 ⁻¹⁰ mg/L	6.1 mg/L

(a) No specific performance objectives for chemical species. Drinking-water units are 10 mg/L.

S.6 Conclusions

This performance assessment has calculated the general population, intruder, and groundwater resource impacts from the disposal of low-level, double-shell tank waste. The results of this analysis indicate that disposal of these wastes in the Grout Disposal Facility will not lead to doses above regulatory performance objectives for the next 1,000 to 10,000 years. Sensitivity studies show the key properties that most significantly impact the magnitude or timing of the results for this performance assessment include the following:

- contaminant retardation coefficients in soils and engineered systems
- degradation of the concrete vault and asphalt barrier, including location and extent of cracks
- recharge rate of water through the disposal system from precipitation or irrigation.

Low water infiltration rates through the soil and disposal system, controlled by climate and barriers, will allow the program to meet regulatory and programmatic performance objectives through 10,000 years. After 10,000 years, hazards presented by the disposal action have been reduced by inventory depletion and sorption such that performance objectives will continue to be met.

)

)

)

Contents

Summary	iii
1.0 Introduction	1.1
1.1 Scope of the Performance Assessment	1.3
1.2 General Characteristics of the Disposal Facility and Its Environment	1.3
1.3 Background Information and Related Analyses	1.4
1.3.1 Comparison to Previous Analyses	1.4
1.3.2 Evolution of Grout Disposal Facility Design	1.6
1.3.3 Related Analyses for the Current Disposal Facility Design	1.7
1.4 Approach to Performance Assessment for the Hanford Grout Disposal Facility	1.8
1.5 Performance Objectives	1.11
1.5.1 Applicable Standards	1.12
1.5.2 Performance Objectives and Scenarios for the Grout Disposal Facility	1.16
1.6 Structure of This Performance Assessment	1.18
2.0 Disposal Facility Description	2.1
2.1 Site Characteristics: Hanford Site and Grout Disposal Site	2.2
2.1.1 Site Location and Cultural Geography	2.2
2.1.2 Demography	2.7
2.1.3 Topography and Physiography	2.11
2.1.4 Ecology	2.14
2.1.5 Climate and Meteorology	2.16
2.1.6 Geology	2.21
2.1.7 Hydrology	2.28

2.1.8 Regional Background Contamination and Site Monitoring	2.39
2.1.9 Seismic Activity	2.43
2.2 Waste Characteristics and Inventory	2.45
2.2.1 Waste Description	2.46
2.2.2 Waste Sources and Volumes	2.47
2.2.3 Expected Waste Composition	2.50
2.2.4 Waste Classification	2.51
2.3 Waste Feed Characterization	2.57
2.3.1 Waste Sources	2.57
2.3.2 Objectives for Feed Characterization	2.57
2.3.3 Overall Sampling Strategy	2.57
2.3.4 Characterization of a Feed Tank	2.58
2.3.5 Characterization of a Candidate Tank	2.59
2.3.6 Waste Characterization Summary	2.59
2.4 Characteristics of Grout	2.60
2.4.1 Components of Grout	2.60
2.4.2 Grout Formulation	2.62
2.4.3 Grout Waste Containment and Source Term Concepts	2.65
2.4.4 Grout Waste Form Summary	2.66
2.5 Waste Treatment and Disposal: Waste Form Processing	2.66
2.6 Grout Disposal Facility	2.70
2.6.1 Concrete Vault and Catch Basin	2.70
2.6.2 Asphalt Barrier	2.73

2.6.3	RCRA Cover	2.73
2.6.4	Disposal Facility Summary	2.75
2.7	Permanent Isolation Barrier	2.75
2.7.1	Barrier Design	2.76
2.7.2	Summary of Barriers	2.78
3.0	Analysis of Performance	3.1
3.1	Background	3.1
3.1.1	Approach	3.4
3.2	Pathways and Scenarios	3.5
3.2.1	Time Periods of Interest	3.5
3.2.2	Pathway Identification and Screening	3.6
3.2.3	Conceptual Model of Environmental Transport Pathways	3.12
3.2.4	Conceptual Model of Environmental Accumulation and Exposure Scenarios ..	3.16
3.2.5	Flow and Transport Models	3.21
3.3	Source Term and Engineered System	3.28
3.3.1	Radionuclide and Chemical Inventories	3.29
3.3.2	Conceptual Description of the Long-Term Performance of the Engineered Disposal System	3.30
3.3.3	Grout and Concrete Vault	3.33
3.3.4	RCRA Flow Grid, Catch Basin, Sump, and Thermal Insulation Board	3.46
3.3.5	Asphalt Barrier	3.48
3.3.6	Permanent Isolation Barrier, RCRA Cover, Gravel Layer and Backfill Soil	3.59
3.4	Unsaturated Sediment and Unconfined Aquifer Pathway	3.65

3.4.1 Water Flow in Unsaturated Sediments	3.66
3.4.2 Sorption	3.71
3.4.3 Boundary and Initial Conditions for the Unsaturated Sediments	3.74
3.4.4 Water Flow in the Unconfined Aquifer	3.75
3.4.5 Transport in the Unconfined Aquifer	3.78
3.5 Modeling Approach and Codes	3.83
3.5.1 Modeling Approach	3.85
3.5.2 Unsaturated Flow and Transport Code: PORFLOW	3.88
3.5.3 Saturated Flow and Pathline Transport Code: SLAEMS	3.93
3.5.4 CCSUMRY-PF	3.94
3.5.5 Dose Calculations: GENII Code	3.96
3.6 Case Descriptions	3.97
3.6.1 Hydraulic and Transport Properties of the Central Sensitivity Case	3.99
3.6.2 Hydraulic and Transport Properties of the Central Compliance Case	3.103
3.6.3 Compliance Cases	3.121
3.6.4 Other Release Scenarios	3.131
3.6.5 Design and Sensitivity Cases	3.134
3.6.6 Summary of Key Assumptions	3.151
3.7 Quality Assurance	3.155
3.7.1 Hanford Environmental Dose Overview Panel	3.155
3.7.2 Westinghouse Hanford Company Quality Assurance	3.155
3.7.3 Pacific Northwest Laboratory Quality Assurance	3.156
3.7.4 Performance Assessment Technical Reviews	3.157

4.0	Results of Analyses	4.1
4.1	Results of Exposure Pathways Analyses	4.1
4.1.1	Intermediate Transport Results for Groundwater Pathway	4.2
4.1.2	Dose Results for Groundwater Pathway	4.12
4.1.3	Dose Analysis for Intruder Scenario	4.22
4.1.4	Results for Other Release Scenarios	4.24
4.2	Sensitivity and Uncertainty Analysis	4.29
4.2.1	Engineered System and Vadose Zone	4.30
4.2.2	Uncertainties in Groundwater Transport	4.48
4.2.3	Groundwater Pathway Dosimetry	4.50
4.2.4	Intruder Scenario Dosimetry	4.51
4.2.5	Sensitivity to Inventory	4.51
4.3	Interpretation of Results	4.53
4.3.1	Initial Physical Properties	4.54
4.3.2	Recharge	4.56
4.3.3	Unknown Future/Degraded Properties	4.56
4.3.4	Inventory	4.57
4.3.5	Groundwater	4.57
4.3.6	Exposure Scenario Dosimetry	4.57
4.3.7	Climate Uncertainty	4.58
5.0	Performance Evaluation	5.1
5.1	Comparison to Performance Objectives	5.1
5.1.1	Protection of the General Public	5.1

5.1.2 Protection of Inadvertent Intruders	5.2
5.1.3 Protection of the Groundwater Resource	5.3
5.2 Changes to the Design of Future Grout Disposal Systems	5.4
5.3 Data and Research Needs	5.5
5.3.1 Neptunium Sorption	5.6
5.3.2 Technetium Release	5.6
5.3.3 Timing and Magnitude of Degradation	5.6
5.3.4 Hydraulic Properties of Grout and Concrete	5.6
5.3.5 Hydraulic Properties of the Asphalt Barrier	5.7
5.3.6 Hydraulic Properties of Gravel Layer	5.7
5.3.7 Waste Inventory	5.7
5.3.8 Additional Modeling	5.8
5.4 Conclusion	5.8
6.0 Resumes of Preparers	6.1
7.0 References	7.1
APPENDIX A - Socioeconomics	A.1
APPENDIX B - Meteorology and Projection of Potential Future Climate for the Grout Project	B.1
APPENDIX C - Geology and Aquifer Characteristics of the Grout Treatment Facility	C.1
APPENDIX D - Ecology	D.1
APPENDIX E - Waste Inventory	E.1
APPENDIX F - Permanent Isolation Barrier and Warning Marker System	F.1
APPENDIX G - Detailed Description of PORFLOW	G.1

APPENDIX H - Verification and Benchmark Testing of the Flow and Transport Codes Used for the Hanford Grout Performance Assessment	H.1
APPENDIX I - GENII Computer Code	I.1
APPENDIX J - Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford	J.1
APPENDIX K - Status Report on Ionic Diffusion Through Asphalt	K.1
APPENDIX L - Measurement of Water Vapor Diffusion Through Asphalt Diffusion Barrier Material	L.1
APPENDIX M - Exposure Scenarios and Sources for Parameters	M.1
APPENDIX N - Sensitivity Analysis for Dose and Exposure Assessment Parameters	N.1
APPENDIX O - A Conceptual Description of the Best Estimate Case	O.1
APPENDIX P - Additional Details of Data, Analysis, and Results	P.1
APPENDIX Q - Best Estimate Crack Predictions for the Grout Vault Engineered Barriers	Q.1
APPENDIX R - Compilation of Responses to Requests for Further Information Made by the Peer Review Panel	R.1

Figures

1.1	Map of the Hanford Site and the Grout Disposal Facility	1.2
1.2	Grout Disposal Facility—Closed Vault Pair	1.5
2.1	Hanford Site in Washington State	2.3
2.2	Hanford Site, Counties, and the Regional Highway Network	2.4
2.3	Hanford Site Map Showing Public Highways	2.5
2.4	Activities at the Hanford Site 200 East and 200 West Area	2.6
2.5	Location of the Grout Treatment Facility in the 200 East Area	2.8
2.6	Aerial View of the Grout Treatment Facility Looking West	2.9
2.7	Population Centers Within 80-km Radius of the Hanford Site	2.10
2.8	Geologic Structures of the Pasco Basin and the Hanford Site	2.13
2.9	Divisions of the Columbia Intermontane Province and Adjacent Snake River Plains Province	2.14
2.10	Landforms of the Pasco Basin and the Hanford Site	2.15
2.11	Generalized Stratigraphy of the Suprabasalt Sediments Beneath the Hanford Site	2.22
2.12	Location Map for the Grout Treatment Facility	2.25
2.13	Geologic Cross Section A-A' for the Grout Treatment Facility	2.26
2.14	Geologic Cross Section B-B' for the Grout Treatment Facility	2.27
2.15	Hydrologic Basins Designated for the Washington State Portion of the Columbia Plateau	2.29
2.16	Location of Water Disposal Ponds on the Hanford Site	2.30
2.17	Hindcast Water Table Map of the Hanford Site, January 1944	2.32
2.18	Hanford Site Water Table Map, June 1989	2.34
2.19	200 Areas Water Table Map, June 1990	2.35

2.20	Isopach Map of the Uppermost Aquifer System	2.36
2.21	Geologic Map of the Water Table	2.37
2.22	Averages for Natural and Human-Produced Sources of Radiation	2.42
2.23	Comparison of Seismic Hazard for Various Regions of the Hanford Site	2.44
2.24	Grout Waste Feed Sources and Volumes	2.48
2.25	Waste Source Volume Distribution for Grout Disposal	2.50
2.26	Overall Waste Feed Sampling Strategy	2.58
2.27	Aerial View of the Grout Treatment Facility Location	2.67
2.28	Grout Treatment Facility	2.68
2.29	Aerial View of the Grout Treatment Facility Showing the Location of 44 Vaults as Forecast in 1990	2.69
2.30	Grout Disposal Facility--Grout Disposal Vault, Cutaway View	2.71
2.31	Grout Disposal Facility--Closed Vault Pair	2.72
2.32	Detail of Grouted Waste Disposal Vault with RCRA Cover	2.74
2.33	Conceptual Permanent Isolation Surface Barrier and Warning Marker System for an Above Grade Application	2.76
2.34	Cross Section of a Conceptual Permanent Isolation Barrier and Warning Marker System	2.77
3.1	Overall Conceptual Model for the Grout Technology Performance Assessment	3.2
3.2	Two-Dimensional Cross Section of Soil Profile	3.3
3.3	Flow Pathline of Contaminated Water to a Downgradient Well for an Irrigated Farm or Garden Scenario Where the Pumping Rate Influences the Flow Field	3.7
3.4	Available Exposure Pathways in the GENII Package	3.11
3.5	Areal View of the Grout Treatment Facility Showing the Location of 44 Vaults as Forecast in 1990; Current Volume Estimates Would Yield 33 Units	3.13

3.6	Three-Dimensional Schematic Showing the Vertical Projection of the Grout Vaults Onto the Water Table of the Unconfined Aquifer	3.14
3.7	Example of Water Retention Characteristics	3.23
3.8	Example of Unsaturated Hydraulic Conductivity Relationship	3.23
3.9	Schematic Drawing Showing the Degradation During the 0- to 100-Year Period, and an Exploded View of Roof-Plank Joint Orientation and Distribution	3.31
3.10	Schematic Drawing Showing the Degradation During the 100- to 10 ³ -Year Period, and an Exploded View of Cracking on Concrete Surfaces	3.32
3.11	Sediment Stratigraphy in the Vicinity of the Grout Site	3.68
3.12	Water Retention Characteristics for Engineered Materials and Unsaturated Sediments	3.72
3.13	Unsaturated Hydraulic Conductivity Relationships for Engineered Materials and Unsaturated Sediments	3.72
3.14	Calibrated Hydraulic Conductivity Distribution for Inhomogeneity Zones	3.77
3.15	Calibrated Unconfined Aquifer Model Based on SLAEMS for June 1984	3.78
3.16	Post-Hanford Conditions Predicted With SLAEMS	3.79
3.17	Water-Table Elevations and Pathlines Predicted With SLAEMS for Current Recharge Conditions	3.80
3.18	Water-Table Elevations and Pathlines Predicted With SLAEMS for 5 cm/yr Recharge Conditions	3.80
3.19	Integration of Computational Methods and Computer Codes Used in the Grout Performance Assessment	3.84
3.20	Numerical Grid Used in PORFLOW for the Grout Performance Assessment	3.91
3.21	Features Within the Model of the Central Compliance Case	3.123
3.22	Features Within the Model of the Central Sensitivity Case	3.135
3.23	Features Within the Model of Sensitivity Case 2.4A	3.144
4.1	Case 1.0: Moisture Content Contours for Vadose Zone at 10,000 Years	4.3

4.2A	Case 1:0, Central Compliance Case: Horizontal Darcy Velocity Contours Within Vadose Zone at 10,000 Years	4.4
4.2B	Case 1:0, Central Compliance Case: Vertical Darcy Velocity Contours Within Vadose Zone at 10,000 Years	4.5
4.3	Relative Concentration Contours for Iodine-129 or Other Species in Transport Group 1A at 1,000 Years in Case 1.0	4.6
4.4	Relative Concentration Contours for Iodine-129 at 10,000 Years in Case 1.0	4.7
4.5	Relative Concentration Contours for Iodine-129 at 50,000 Years in Case 1.0	4.8
4.6	Fractional Release to the Groundwater Per Year for Case 1.0	4.10
4.7	Concentrations in Groundwater for Key Radionuclides	4.11
4.8	Case 1.0, Central Compliance Case: Breakdown of Farm Scenario Dose by Radionuclide	4.13
4.9	Compliance Cases: Farm Scenario Dose	4.14
4.10	Case 1.0, Central Compliance Case: Breakdown of Garden Scenario Dose by Radionuclide	4.16
4.11	Garden Scenario: Doses for Compliance Cases	4.17
4.12	Case 1.0, Central Compliance Case: Drinking-Water Dose to Maximum Individual	4.18
4.13	Drinking-Water Doses for Compliance Cases	4.19
4.14	Population Dose Versus Time for River Scenario for Compliance Cases	4.22
4.15	Population Dose for Community Well Scenario Versus Time for Compliance Cases	4.23
4.16	Predicted Activity in Grout of Radionuclides in the Uranium-238 Decay Chain	4.25
4.17	Predicted Rate of Radon Generation in Grout	4.25
4.18	Relative Soil Concentrations Versus Time for Transport Groups with Zero Recharge	4.27
4.19	Doses for Garden Scenario Resulting from Upward Diffusion with Zero Recharge	4.27
4.20	Estimated Dose in the Farm Scenario Versus Time for a Staged Degradation of the Engineered System with Recharge Rate of 5 cm/yr	4.29

WHC-SD-WM-EE-004, Rev. 1

4.21	Fractional Release by Group Versus Time for Central Sensitivity Case	4.31
4.22	Farm Scenario Dose Versus Time for Central Sensitivity Case	4.32
4.23	Fractional Release Curves for Less Important Transport Groups	4.33
4.24A	Moisture Content Contours for the Central Sensitivity Case at 10,000 Years	4.34
4.24B	Moisture Content Contours for the Central Sensitivity Case Showing Top Portion of Vault at 1,000 Years	4.35
4.25	Relative Concentration Contours for Iodine-129 in the Central Sensitivity Case at 10,000 Years	4.36
4.26	Farm Scenario Doses for Design Cases	4.38
4.27	Sensitivity of Results to Assumptions Involving Grout	4.40
4.28	Sensitivity of Results to Assumptions Involving Asphalt Barrier	4.41
4.29	Farm Scenario Dose for Sensitivity Cases Involving Cracking Assumptions	4.43
4.30	Farm Scenario Dose for Sensitivity Cases Involving the RCRA Cover	4.45
4.31	Comparison of Farm Scenario Doses Calculated for the Central Sensitivity Case with and Without a Vapor Diffusion Water Source	4.46
4.32	Comparison of Farm Scenario Doses for Case 2.6B and Case 2.0	4.47

Tables

2.1	Provisional Background Values for Hanford Site Groundwater	2.40
2.2	Dose Summary from Hanford Site Operations	2.42
2.3	Approximate Probability of Exceedance During Selected Time Periods for Three Ground Motions	2.45
2.4	Waste Components Analyzed in This Performance Assessment	2.52
2.5	Compositions of Representative Grout Dry Blend Materials, Wt%	2.63
2.6	Representative Grout Formulations	2.64
2.7	Partial List of Grout Formulation Criteria	2.64
2.8	Nitrate Leachability and Compressive Strength for Laboratory-Prepared and Pilot-Scale 106-AN Grout Samples	2.65
2.9	Vertical Layering and Materials of the Protective Barrier	2.78
3.1	Events Investigated for Potential Impact on Waste Disposal Systems	3.8
3.2	Specific Species/Grout Combinations for Which Effective Diffusion Coefficients were Measured	3.34
3.3	Initial Source Parameters for the Asphalt Barrier, Concrete Vault, and Grout in the Nondegraded Engineered System	3.37
3.4	Initial Hydraulic Properties for Grout	3.39
3.5	Comparison of Aggregate for the Vault Concrete Mix Design to Literature-Reported Values for Concrete	3.41
3.6	Comparison of Saturated Hydraulic Properties for Concrete: Hanford and Whiting	3.41
3.7	Initial Hydraulic Properties for Concrete	3.41
3.8	Literature Values for Diffusion Through Asphalt	3.50
3.9	Asphalt Diffusivity from Concentration Profile in Asphalt Following Immersion Test	3.52
3.10	Effective Diffusion Coefficients from ANS 16.1 Leach Tests of Compacted Asphalt Barrier Material	3.52

3.11	Hydraulic Properties for the van Genuchten-Mualem Model Applied to the Asphalt Barrier	3.53
3.12	Processes Anticipated to Cause Asphalt Barrier Degradation	3.57
3.13	Hydraulic Properties for the RCRA Cover, Gravel Layer and Backfill Soil	3.62
3.14	Effective Diffusion Coefficient Parameters for Modeling Diffusive Transport in Unsaturated Soils and Engineered Materials	3.64
3.15	Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments	3.65
3.16	Hydraulic Properties for Engineered Materials and Unsaturated Sediments	3.71
3.17	Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments	3.73
3.18	Boundary Conditions for the Flow and Transport Analyses of Grout Performance	3.74
3.19	Summary of Initial Conditions for Analysis of Flow	3.75
3.20	Summary of SLAEMS Model Simulations	3.81
3.21	Plume Intercept Width at 100 m Upgradient of a Pumping Well	3.82
3.22	Summary of Hydraulic and Transport Properties for the Central Sensitivity Case	3.101
3.23	Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments	3.102
3.24	Crack Size/Spacing as a Function of Time for the Asphalt Barrier	3.106
3.25	Size of Asphalt Corner Crack as a Function of Time	3.106
3.26	Crack Size/Spacing as a Function of Time for Reinforced Concrete	3.107
3.27	Saturated Hydraulic Conductivity and Porosity of the Asphalt Barrier	3.108
3.28	Saturated Hydraulic Conductivity and Porosity of the Asphalt Corner Cracks	3.109
3.29	Saturated Hydraulic Conductivity and Porosity of Reinforced Concrete	3.110
3.30	Saturated Hydraulic Conductivity and Porosity of Grout	3.111
3.31	Unsaturated Hydraulic Characteristics of the Asphalt Barrier	3.111
3.32	Unsaturated Hydraulic Characteristics of Asphalt Corner Cracks	3.112

3.33	Unsaturated Hydraulic Characteristics of Reinforced Concrete	3.112
3.34	Unsaturated Hydraulic Characteristics of Grout	3.113
3.35	Effective Diffusion Coefficients for the Asphalt Barrier	3.114
3.36	Effective Diffusion Coefficients for Asphalt Corner Cracks	3.115
3.37	Effective Diffusion Coefficients for Reinforced Concrete	3.115
3.38	Source Strength of Water Vapor Diffusion for Generalized Cracks/Biodegradation and Associated Surface Exposure	3.119
3.39	Calculated Source Strength of Water Vapor Diffusion for Asphalt Corner Cracks/Biodegradation and Associated Surface Exposure	3.120
3.40	Source Strength of Water Vapor Diffusion for Generalized Cracks and Biodegradation as a Function of Time Interval and Associated Surface Exposure	3.121
3.41	Source Strength of Water Vapor Diffusion for Asphalt Corner Cracks and Biodegradation as a Function of Time Interval and Associated Surface Exposure	3.121
3.42	Detailed Parameter Inputs Used in Modeling the Central Compliance Case	3.125
3.43	Radio Nuclides Important to Radon Generation	3.131
3.44	Detailed Parameter Inputs Used in Modeling the Central Sensitivity Case	3.137
3.45	Features of the Design Cases	3.139
3.46	Features of the Sensitivity Cases	3.141
3.47	Inventory Sensitivity Cases for the Groundwater Pathway	3.149
3.48	Inventory Sensitivity Cases for the Intruder Scenarios	3.150
4.1	Differences in Compliance Case Simulations	4.2
4.2	Summary of Dose Results for Compliance Cases	4.12
4.3	Concentrations of Primary and Secondary Drinking-Water Chemicals in the Aquifer	4.20
4.4	Impacts for Drilling Intrusion Scenario	4.23
4.5	Impacts for Post-Drilling Residential Scenario	4.24

WHC-SD-WM-EE-004, Rev. 1

4.6	Well Intercept Factors as a Function of Recharge, Pumping Rate, and Number of Vaults	4.48
4.7	Impact of Maximum Inventory Sensitivity Case on Dose for the Central Sensitivity Case Farm Scenario	4.52
4.8	Sensitivity to Inventory for Drilling Intrusion and Post-Drilling Habitation Scenarios	4.53
5.1	Comparison to Performance Objectives for Protection of the General Public	5.2
5.2	Comparison to Performance Objective for Protection of Intruders	5.3
5.3	Comparison to Performance Objective for Groundwater Protection	5.4

1.0 Introduction

The Hanford Site in Washington State (Figure 1.1), owned by the U.S. government, has been used extensively as a defense materials production facility by the U.S. Department of Energy (DOE) and its predecessor organizations, the U.S. Atomic Energy Commission and the U.S. Energy Research and Development Administration. Since the 1940s, operations at the Site have been dedicated to the production of nuclear materials (primarily plutonium) and electricity, to diverse research, and to waste management activities. During the course of operations, the Site has accumulated an inventory of radioactive waste and mixed waste containing both radioactive and chemically hazardous constituents. Because of decreasing defense-related needs for plutonium, production operations at the Site have ceased and the Site's mission is now directed toward environmental restoration and energy-related research and technology development. In conjunction with this new mission, DOE is proceeding with plans to permanently dispose of radioactive and mixed waste that has accumulated over the last 50 years, much of which is temporarily stored in single- and double-shell tanks on the Site. Based on the Record of Decision for the Hanford Defense Waste Environmental Impact Statement (HDWEIS, U.S. DOE 1987), the waste currently stored in selected double-shell tanks will be pretreated to separate the low-level liquid fraction from the high-level and transuranic waste, which ultimately will be sent to a high-level waste repository for permanent disposal. The low-level liquid fraction will then be combined with liquid waste from other Hanford Site operations for onsite disposal in the Grout Disposal Facility, a near-surface disposal system designed to contain low-level liquid radioactive and mixed wastes in a solid cement-like form.

The purpose of this report is to present the performance assessment for the Grout Disposal Facility at the Hanford Site in accordance with DOE Order 5820.2A (U.S. DOE 1988a), the primary regulation governing management and disposal of radioactive waste at DOE facilities. The Order requires that "field organizations with disposal sites shall prepare and maintain a site-specific radiological performance assessment for the disposal of waste for the purpose of demonstrating compliance with performance objectives . . ." In the Order, performance assessment is defined as ". . . a systematic analysis of the potential risks posed by waste management systems to the public and environment, and a comparison of those risks to established performance objectives."

This performance assessment describes the models, methods, and data used to evaluate long-term performance of the grout disposal system. The results of the assessment are presented and compared to performance objectives established for disposal of low-level radioactive waste. As plans for cleanup of the Hanford Site proceed, the characteristics of the waste streams or the design of the Grout Disposal Facility itself may undergo changes from those described in this performance assessment, in which case the analysis would be updated as necessary.

S9211085 51

Figure 1.1. Map of the Hanford Site and the Grout Disposal Facility

1.1 Scope of the Performance Assessment

The Grout Disposal Facility comprises the final disposal system for low-level liquid waste from double-shell tanks that has been incorporated into grout. It is part of a larger complex known as the Grout Treatment Facility, which also includes radioactive waste transfer equipment, dry materials storage capability, and the Grout Processing Facility. This analysis pertains only to the long-term performance assessment of the Grout Disposal Facility following the facility's final closure. Disposal of the hazardous waste components under the Resource Conservation and Recovery Act (RCRA), and operational safety issues related to processing and disposal of the waste, are addressed in separate analyses (see Section 1.3.3).

The wastes to be disposed at the Grout Disposal Facility consist of low-level radioactive and mixed liquid wastes from a variety of sources at the Hanford Site, including operations at N Reactor, the 200 Area chemical separations areas, and other Hanford facilities such as the 300 Area fuel fabrication facilities and miscellaneous laboratories. Approximately half of the waste consists of the low-level liquid fraction of pretreated high-level and transuranic wastes that result from reprocessing irradiated production reactor fuel and producing plutonium metal. All of these wastes will be stored in the double-shell tanks at some time prior to final disposal. The wastes may be pretreated by a variety of processes either to concentrate dilute liquids or remove specific radionuclides from more concentrated waste streams. The liquid waste to be incorporated into grout has a relatively high concentration of dissolved salts and suspended solids, and contains a number of inorganic chemical species that are regulated as hazardous waste under RCRA. Although this performance assessment is primarily concerned with the radioactive constituents in the waste, an abbreviated analysis of regulated nonradiological components is also presented for completeness.

1.2 General Characteristics of the Disposal Facility and Its Environment

The Hanford Site is located in a semiarid region of southeastern Washington State. The surrounding area is primarily agricultural. The Site is bounded on the north and east by the Columbia River, and by the Rattlesnake Hills to the southwest. The cities of Richland, Pasco, and Kennewick are located at the southeast corner of the Site. The Grout Disposal Facility is being constructed adjacent to the eastern boundary of the 200 East Area, approximately in the center of the Hanford Site (see Figure 1.1). Chapter 2 of this document provides a complete description of the Grout Treatment Facility and its environment, characteristics of the waste to be disposed at the site, and the components of the disposal system.

The geology of the Hanford Site is characterized as heterogeneous gravelly, sandy, or silty sedimentary deposits overlying a foundation of basalt and clay formations. The 200 East Area sits on a plateau that is elevated from the Columbia River plain, and is bounded by several basalt formations protruding above the soil surface. An unconfined aquifer underlies much of the Hanford Site at the interface

between the upper sedimentary strata and the relatively impermeable basalt or clay formations below. Groundwater in the unconfined aquifer beneath the 200 Areas flows generally toward the north and east to the Columbia River.

The Grout Disposal Facility is designed as a near-surface burial ground consisting of sealed reinforced concrete vaults that provide primary containment for the grouted waste. The vaults are designed to meet RCRA requirements for double containment, including a concrete catch basin filled with gravel beneath each vault. The catch basin permits monitoring of any liquid leaching from the vaults during the RCRA monitoring period (approximately 30 years). The vaults will be nearly filled with grouted waste, which will be capped with nonradioactive grout. The vault will also be covered with concrete blocks and a prestressed concrete lid. The entire vault will be surrounded by an asphalt barrier consisting of an asphalt-aggregate mixture compacted to approximately 4% void space (hereafter referred to as the "asphalt barrier"). For each pair of vaults there will be a gravel layer over the top of the asphalt barrier and a sloped RCRA cover containing soil and bentonite clay. The entire disposal facility will also be protected by a multilayered barrier which is being designed to minimize water infiltration; wind erosion; and intrusion by plants, animals, and people over an extended period. The components of the disposal system were developed over a number of years to minimize infiltration of precipitation through the burial site and to prevent diffusion of water vapor from the surrounding soil into the vaults. A schematic drawing of the disposal system is shown in Figure 1.2.

1.3 Background Information and Related Analyses

Over the past 10 years, scientific and engineering studies have been conducted to characterize the grout disposal system, including the radionuclide inventory in the waste, the grout formulation, the design of the engineered barrier system, and the long-term material properties of the grout and barrier components. The following sections summarize these studies and describe their relationship to the current disposal system design.

1.3.1 Comparison to Previous Analyses

Various documents have addressed environmental aspects of defense waste management at the Hanford Site. The most relevant of these include the *Final Environmental Impact Statement - Disposal of Hanford Defense High Level, Transuranic, and Tank Wastes* (HDWEIS, U.S. DOE 1987) and *Long-Term Performance Assessment of Grouted Phosphate/Sulfate Waste from N Reactor Operations* (Sewart et al. 1987).

The HDWEIS was a programmatic decision-making document that provided analyses of environmental impacts for selecting final disposal strategies for the high-level, transuranic, and tank wastes generated during national defense-related work and currently stored at the Hanford Site. The physical and

Figure 1.2. Grout Disposal Facility—Closed Vault Pair

chemical characteristics of the waste forms considered in this document are highly diverse and the waste had not been completely characterized at the time the document was prepared. The waste forms include liquid waste in double-shell tanks, vitrified wastes in steel canisters (from processed double-shell tank wastes), sludge and salts in the single-shell tanks, strontium and cesium capsules in transport containers, pre-1970 wastes previously disposed in various forms, and grout containing low-level liquids from processing of double-shell tank waste. This performance assessment updates and expands the analysis presented in the HDWEIS to include new design elements in the Grout Disposal Facility and additional information about the waste composition.

The performance assessment of grouted phosphate/sulfate waste (PSW) served as input to the *Environmental Assessment for the Grouting and Near-Surface Disposal of Low-Level Radioactive Phosphate/Sulfate Waste from N Reactor Operations* (U.S. DOE 1986a). This document analyzed the long-term performance of PSW grout disposal in terms of 1) potential incremental increases of regulated chemicals in groundwater and in the Columbia River, and 2) potential incremental radiation doses to a person who either intrudes directly into a grout monolith or who uses groundwater contaminated by the long-term

release of PSW radionuclides. The waste analyzed in the report is a low-level radioactive waste generated by decontamination operations and other activities associated with operation of the N Reactor on the Hanford Site. Disposal of these wastes has been completed. This performance assessment presents a more comprehensive analysis, including wastes that were not evaluated in the PSW performance assessment.

1.3.2 Evolution of Grout Disposal Facility Design

The current design of the grout disposal system analyzed in this document has evolved in part through an iterative process incorporating a number of preliminary performance assessment activities. The original concept called for disposal of the low-level tank wastes as a grout slurry that would be pumped into large subsurface, reinforced concrete vaults. After the grout slurry had hardened and cured, the remaining space within the vault would be filled with a nonradioactive grout. To meet the requirements for hazardous waste disposal as defined in RCRA, the vaults were designed to include double liners, a leachate detection and collection system, and a cap to divert water that infiltrates through the soil away from the wastes. At the time of closure, a surface barrier would be placed over the entire site to reduce the quantity of water percolating through the soil and to prevent intrusion into the disposal site.

This basic disposal system design was analyzed in the HDWEIS (U.S. DOE 1987, Appendix D) and in the performance assessment prepared for the disposal of grouted PSW from N Reactor operations (Sewart et al. 1987). One vault was constructed according to this design and was successfully filled in 1988 and 1989 with 5,300,000 L (1,400,000 gal) of grouted PSW waste. This grout was recently sampled and characterized, and it met all performance criteria established for that analysis (Huang, Mitchell and Conner 1993).

During the time when the HDWEIS and the PSW performance assessment were being completed, a preliminary performance assessment was prepared for double-shell slurry feed (DSSF), the waste scheduled to be grouted following grouting of the PSW wastes. This preliminary assessment analyzed four different engineered disposal systems, including 1) grout in a vault (called a "bare monolith"), 2) a grout/vault monolith covered by a surface barrier to reduce recharge through the disposal site, 3) a grout/vault monolith encased in a diffusion barrier consisting of gravel or asphalt to prevent water from contacting the monolith and to slow diffusion of contaminants from the vault, and 4) a grout/vault monolith encased in the asphalt or gravel barrier and covered with the surface barrier. The only design that met the proposed groundwater protection objective (based on drinking-water dose) was that for the disposal system incorporating the grout monolith, vault, asphalt or gravel barrier, and surface barrier.

Based on that preliminary performance assessment, the design of the grout disposal system was revised to include a diffusion barrier surrounding the grout/vault structure. Construction limitations required that the catch basin, which provides the secondary containment required of a RCRA disposal system, be added beneath the grout vault. The original concept for the diffusion barrier called for 91.4 cm (36 in.) of gravel. However, laboratory testing revealed that the maximum allowable diffusivity could not be achieved with gravel alone. Asphalt-coated gravel met the diffusivity requirement and was

incorporated into the disposal system design. Asphalt was selected because it is hydrophobic, and it is expected to exhibit long-term durability in a natural subsurface environment. A preliminary performance assessment based on this revised design showed that the performance objectives for the grout disposal system would be met.

The latest change in the grout disposal system was made when water-vapor return was identified as a mechanism by which water could contact the wastes and lead to potentially significant releases of contaminants from the disposal system (Cary, Gee and Whyatt 1991; Appendix L). Because of the high ionic strength of liquids in the grout, diffusion of vapor from more dilute moisture in the surrounding soil could cause water to accumulate at the vault surface. To slow this vapor diffusion process, the material used for the diffusion barrier was changed from asphalt-coated gravel to an asphalt/aggregate mix similar to that used in highway pavements. Vapor and ionic diffusion rates through this mix were determined to be low enough to ensure that performance objectives would be met. This analysis was conducted to determine the magnitude of vapor diffusion in the absence of other sources of water infiltration. In relative terms, vapor diffusion would account for a relatively small fraction of the water that contacts the grouted waste. Also, the thickness of the diffusion barrier was increased to 102 cm (40 in.) to ensure that the barrier would retain a minimum 91.4-cm (36-in.) thickness after allowing for biodegradation over 10,000 years.

Because the next four vaults to be filled were under construction when water vapor return was identified as a potential release mechanism, the diffusion barrier beneath the catch basins for those vaults is composed of a 46-cm- (18-in. minimum) thick layer of the asphalt/aggregate pavement on top of another 46-cm-thick layer of asphalt-coated gravel. The current design calls for future vaults to be constructed with a minimum 100-cm-thick layer of the asphalt/aggregate pavement surrounding the vaults, including the layer beneath the catch basin.

Using information obtained from the previous analyses, the engineered grout disposal system has evolved into the design analyzed in this performance assessment. The major components of the system are the grouted waste, the lined, reinforced concrete vault structure with a catch basin, an asphalt barrier surrounding the vault, a RCRA cover, and a surface barrier to be placed at the time of site closure. The details of this engineered grout disposal system are presented in Chapter 2.

1.3.3 Related Analyses for the Current Disposal Facility Design

This performance assessment is one of three primary documents for the Hanford Grout Disposal Program. This performance assessment provides an analysis of the potential long-term impacts resulting from low-level waste disposal. The other two major program documents are the final safety analysis report (FSAR) (in preparation) and the RCRA Part B permit application (U.S. DOE-RL 1992a). The three documents differ in their scope and objectives, although they are interrelated because they describe the same waste and disposal system.

The scope of the FSAR includes evaluation of safety concerns for all the operating facilities at the Grout Treatment Facility through the time of vault closure and required RCRA monitoring (approximately 30 years). The operating facilities include the Dry Materials Storage Facility, the Grout Processing Facility, the feed transport system, and the Grout Disposal Facility. The FSAR is written to assure compliance with DOE Order 5480.5, "Safety of Nuclear Facilities" (U.S. DOE 1986b). This Order requires a safety analysis and review process that includes a formal, documented system for identifying, evaluating, and controlling risks to workers, the public, and the environment. This is accomplished through the preparation, independent review, and approval of a final safety analysis (the FSAR), which must be completed before facility operations commence.

The RCRA Part B permit application is written to comply with Washington State Department of Ecology regulations for the treatment, storage, and disposal of hazardous waste in compliance with WAC-173-303 (WAC 1989) and the RCRA of 1976. The Part B permit application documents compliance with design, construction, and operation of the Grout Processing Facility, feed transport system, and Grout Disposal Facility up to the time of closure of the Grout Disposal Facility (approximately 30 years).

The performance assessment provides an evaluation of long-term environmental impacts beyond the operational and maintenance periods covered by the FSAR and the RCRA permit. It evaluates those features of the disposal system and its surroundings that control release of radionuclides and hazardous chemicals from the Grout Disposal Facility to the environment over the long term.

1.4 Approach to Performance Assessment for the Hanford Grout Disposal Facility

Performance of the disposal system for grouted liquid waste at the Hanford Site is assessed using a multi-step approach. First, a conceptual model is developed to describe the engineered disposal system and its environmental setting as completely as possible. Because performance of the system must be projected over time periods during which direct monitoring of the disposal site is not feasible, the conceptual model is used to select the most applicable mathematical models and data that will be used to predict the system's long-term performance and associated uncertainties.

Second, transport and exposure scenarios are defined to describe credible conditions that could result in exposure of humans to hazardous components in the waste after disposal. The release and transport of waste components from the disposal site to potential receptors is then predicted based on the conceptual model defined for the disposal system and its environment.

Finally, the consequences associated with each scenario are estimated based on the conceptual model for human exposure, and they are compared with performance objectives established for the disposal system. The results of the analysis are ultimately used to make decisions regarding the adequacy of

the disposal system to protect public health and safety over the long term. The evaluation may also identify needs for additional information, a different modeling approach, or modifications to the disposal system design. In such cases, the performance assessment becomes part of an iterative process by which the disposal system design and the assessment itself are revised as needed to produce a technically consistent and credible evaluation of the disposal system's long-term performance.

Performance assessments for radioactive waste disposal facilities must attempt to predict their potential impacts over time periods for which there are no directly applicable experimental or operational data. Because observations made over a relatively short period must be used to predict long-term performance of a specific disposal system, such an analysis is subject to significant uncertainty. Major potential sources of uncertainty include 1) incomplete initial characterization of the waste and radionuclide inventory, 2) difficulty in predicting long-term material properties of the waste form and the engineered containment barriers, 3) limitations in understanding transport of waste components over the long term, 4) unpredictable environmental conditions, and 5) selection of appropriate parameters associated with the exposure scenarios to be analyzed. These uncertainties may be accounted for in a number of ways, depending on the purpose and level of sophistication in the analysis. Possible approaches include:

1. using conservative assumptions in all phases of the analysis to demonstrate that performance objectives are met even under "credible worst case" conditions,
2. using statistical sampling methods to quantify the uncertainties and assign probabilities to a particular set of outcomes,
3. defining a "best estimate" case that describes the expected behavior of the disposal system and its environment in the future, and
4. defining a set of cases that represent a reasonable range of conditions expected over the period of the analysis.

The first approach is not recommended by DOE because it results in an unrealistic estimate of the potential impacts from radioactive waste disposal. The second approach is a substantially more complex analysis than is required for this performance assessment, and the information about uncertainties in many parameters is not sufficient to perform such an analysis. The performance assessment was initiated with the intent to use the third approach; however, significant uncertainty regarding the degradation mechanisms, rates of degradation, and material properties of the waste and engineered barriers over time made it impossible to justify a single best estimate case at this time (see Appendix Q). The fourth approach was adopted as the primary method for this performance assessment in order to account for uncertainties in the properties of the waste and engineered barriers as these system components degrade over time.

The conceptual model developed for this assessment resulted in the use of separate computer simulations for groundwater transport in the unsaturated and saturated zones and for human exposure pathways. The groundwater transport calculations were performed for unit concentrations of radionuclides

and chemical species in the waste to obtain estimates of fractional release over time. A second set of calculations converted the fractional release estimates to concentrations in groundwater using the projected waste inventories, radioactive decay rates, and groundwater dilution factors appropriate to each case. The groundwater concentrations were converted to dose estimates by a third set of calculations using unit dose factors specific to each exposure scenario evaluated in the performance assessment. Because of the modular nature of the analysis, the uncertainties associated with each aspect of the analysis were evaluated separately.

The uncertainties associated with the initial waste inventories are based on a range of estimates obtained from several different sources, including direct analysis of the waste to be grouted, an onsite inventory database, operational limits related to heat production, regulatory limits for waste disposal, or site production records. As part of the evaluation, separate sensitivity analyses were also conducted to identify the most significant parameters for unsaturated zone groundwater transport, and for human exposure and dose estimates.

In the groundwater transport sensitivity analysis, a central sensitivity case and a set of related cases were defined to investigate the influence of changes in characteristics for various components of the waste and disposal system and for long-term climate change. These cases did not necessarily represent realistic estimates for disposal system performance, but were simplified conceptual models designed to evaluate the effect of various parameters on transport of radionuclides from the disposal system. The central sensitivity case used a simplified model of the disposal system in an initially degraded state as the reference point for other cases in the sensitivity analysis. The other sensitivity cases generally evaluated the effect of changes in one or two parameters at a time, relative to the central case, assuming that they remained constant over time.

Results from the transport sensitivity analysis were ultimately used to help define a range of "compliance" cases that approximate the expected disposal system performance in this assessment.

The compliance cases represented the disposal system's expected behavior over time, using a somewhat more complex conceptual model than the sensitivity cases. In these cases, the critical properties of multiple components were assumed to vary simultaneously over time as the engineered system degrades. The predicted consequences from this set of compliance cases are compared to the performance objectives established for the performance assessment, and which are described in the following section.

In contrast to the sensitivity analysis for groundwater transport, the sensitivity analysis for the dose and exposure pathways employed a more classical approach involving definition of probability distributions for all parameters input to the model for each exposure scenario. A statistical sampling technique was used to select a set of input parameters from these distributions for each of a predetermined number of trial calculations. The results from all trials were then evaluated to determine which parameters exerted a significant influence on the total uncertainty associated with the dose estimate.

In the analysis of compliance cases for comparison to performance objectives, and for evaluation of the groundwater transport sensitivity cases, a single deterministic dose estimate was developed based on the best available estimate for each parameter in the pertinent exposure pathways. In order to interface with the results of the groundwater transport analysis, a single estimate was defined for the dose contributed by each radionuclide in a given scenario. The outputs from the transport and exposure simulations were then combined to obtain dose estimates reported in this document. The dose estimates presented in this performance assessment represent only the predicted impacts of the Grout Disposal Facility, therefore they are incremental doses in addition to those from background radionuclides or from other Hanford Site facilities. Details of the transport and dose calculation methods, including the sensitivity analyses, are presented in Chapter 3 of this document. Results of the analyses and estimates of their associated uncertainties are discussed in Chapter 4 and Appendix N.

1.5 Performance Objectives

Performance objectives have been established for this performance assessment to provide reasonable assurance that the proposed disposal of grouted waste will not constitute an unacceptable risk to members of the public in the future. Performance objectives are quantitative criteria that can be compared with the estimated consequences of a particular waste management alternative. They may be derived from regulatory requirements established by DOE or other government agencies, or they may be engineering design criteria adopted during the planning phase for a particular facility. The following section outlines the basic requirements and applicable regulations for setting performance objectives in a site-specific performance assessment. Section 1.5.2 then defines the applicable performance objectives for this performance assessment and describes how the predicted performance of the Grout Disposal Facility will be evaluated relative to the performance objectives.

DOE Order 5820.2A, Chapter III, provides the basic framework for criteria that must be met as part of a performance assessment in order to provide a basis for evaluating the risks associated with management of low-level radioactive waste at a particular facility. At minimum, DOE Order 5820.2A provides that performance objectives must accomplish the following:

1. Protect public health and safety in accordance with standards specified in applicable . . . DOE Orders.

2. Assure that external exposure to the waste and concentrations of radioactive material which may be released into surface water, groundwater, soil, plants and animals results in an effective dose equivalent^(a) that does not exceed 25 mrem/yr to any member of the public. Releases to the atmosphere shall meet the requirements of 40 CFR 61. Reasonable effort should be made to maintain releases of radioactivity in effluents to the general environment as low as is reasonably achievable.
3. Assure that the committed effective dose equivalents received by individuals who inadvertently may intrude into the facility after the loss of active institutional control (100 years) will not exceed 100 mrem/yr for continuous exposure or 500 mrem for a single acute exposure.
4. Protect ground water resources, consistent with Federal, State and local requirements.

In addition, the Order provides that "DOE-low-level waste that contains non-radioactive hazardous waste components (mixed waste) shall . . . be regulated by the appropriate regional authorities under the Resource Conservation and Recovery Act." The application of each of these requirements to the Grout Disposal Facility at Hanford is discussed in the following section.

1.5.1 Applicable Standards

In addition to the quantitative standards provided directly by DOE Order 5820.2A, the Order refers to other regulations that must be considered in establishing performance objectives for low-level radioactive waste disposal. Among these are other DOE orders, including DOE's policy to keep releases of radioactive materials to the environment "as low as reasonably achievable" (ALARA); the Clean Air Act National Emission Standards for Hazardous Air Pollutants (NESHAP; 40 CFR 61); and groundwater protection standards established by other federal, state, or local authorities. The requirements of RCRA as

-
- (a) In ICRP Publication 26 (ICRP 1977a), the International Commission on Radiological Protection introduced the effective dose equivalent as the sum of the dose equivalents in individual organs H_T , each weighted by an organ-weighting factor w_T :

$$H_E = \sum_T w_T H_T$$

The organ-weighting factors were chosen by the Commission to reflect the relative risk of death from cancer or occurrence of severe hereditary effects in the first two generations after uniform whole body exposure (ICRP 1979).

implemented by individual states also apply to facilities that manage mixed waste containing nonradioactive hazardous materials. The following sections summarize provisions of each of these additional regulations.

DOE Orders. DOE Order 5820.2A outlines the basic framework of requirements for radioactive waste management; however, it draws upon concepts developed in other DOE Orders in implementing those standards. DOE Order 5400.5 (U.S. DOE 1990a) provides the basic regulations for radiation protection of the public and the environment at operating DOE facilities, and it is in this Order that the ALARA process is described. From the definition in DOE Order 5400.5, "As Low As Reasonably Achievable (ALARA) is a term used to describe an approach to radiation protection to control or manage exposures (both individual and collective to the work force and the general public) and releases of radioactive material to the environment as low as social, technical, economic, practical, and public policy considerations permit."

The DOE Richland Operations Office (RL) has also issued an Order designated DOE-RL 5820.2A (U.S. DOE-RL 1990) to establish "Hanford-specific policies, guidelines, and requirements by which the U.S. Department of Energy, Richland Operations . . . manages its radioactive waste, mixed waste and contaminated facilities." This Order supplements the basic requirements of DOE 5820.2A and provides additional information on how those standards should be applied. Regarding the establishment of performance objectives for low-level radioactive and mixed waste disposal at the Hanford Site, DOE-RL 5820.2A, Chapter III, Section 3a supplies the following guidance:

Performance Objectives. Disposal systems for LLW (low-level waste) disposed of on or after 09-26-88 shall be designed to meet the following objectives in accordance with schedule guidance in DOE-RL 5820.2A, Chapter III, Paragraph 3a.

1. **General Public Protection.** Disposal systems shall be designed to ensure that exposure to any member of the public that results from disposal of solid LLW shall not exceed 25 mrem/yr effective dose equivalent (EDE) through all exposure pathways for at least 1,000 years after disposal. The point of compliance shall be no further from the edge of the waste than the Hanford Site boundary during the period of active institutional control. After the active institutional control period (assumed to be not more than 100 years) the point of compliance shall be not more than 100 meters from the edge of the disposal site.
2. **Groundwater Protection.** Disposal systems shall be designed to ensure that disposal of LLW after 9-26-88 does not result in concentrations of radionuclides (above existing levels) in groundwater exceeding those corresponding to an EDE of 4 mrem/yr to any person who might drink 2 liters per day of water from a well drilled into the aquifer, for at least 1,000 years after disposal. The point of compliance shall be no further than 100 meters from the edge of the waste.

3. **ALARA (Long-Term Protection).** Reasonable effort shall be made to design disposal systems in such a way that potential exposures are ALARA for all times up to the year of maximum exposure. If the predicted population exposure is less than 500 person-rem/yr in the year of maximum exposure, the ALARA requirement is defined to have been complied with.
4. **Intruder Protection.** Disposal closure systems shall be designed to ensure that exposure to individuals who inadvertently intrude the closed facility after the active institutional control period shall not exceed 100 mrem/yr for continuous exposure, or 500 mrem for a single acute exposure. For wastes that may remain hazardous to inadvertent intruders beyond 100 years, passive controls (e.g., long-term Government ownership and control, appropriate markers and barrier systems) shall be incorporated to provide reasonable assurance that inadvertent intruders will be warned and deterred from disturbing the site for up to 500 years.
5. **Mixed-Waste Regulations.** Disposal systems shall be designed to meet the applicable requirements of 40 CFR 264 and 265, and WAC 173-303 [WAC 1989] for the disposal of LLW-MW [low-level waste-mixed waste]. [These regulations represent the federal RCRA requirements, and Washington State's implementation of RCRA, respectively.]

Clean Air Act (40 CFR 61). The 1989 amendments to the Clean Air Act establish National Emission Standards for Hazardous Air Pollutants (NESHAP), including radionuclides released to the atmosphere from DOE facilities. Subpart H of 40 CFR 61 regulates airborne emissions of all radionuclides except radon from operating DOE facilities, and specifies a 10-mrem/yr dose standard for the maximally exposed offsite individual via the air pathways only. Subpart Q addresses radon emissions from DOE storage and disposal facilities that contain radium (except for uranium mill tailings, which are covered under a separate regulation). This regulation specifies a flux standard for radon-222 of 20 pCi/m²-s averaged over the area of the facility.

The 10-mrem/yr standard for air pathways under Subpart H of 40 CFR 61 applies to airborne emissions of radionuclides other than radon from operating facilities under DOE control. Because the Grout Disposal Facility will not generate significant quantities of airborne effluents other than radon after the institutional control period, this subpart of the standard does not apply. Any airborne radionuclide emissions during the operational and institutional control phases of the Grout Disposal Facility will be assessed in conjunction with the applicable Clean Air Act permitting and reporting requirements, and they will not be considered as part of this performance assessment. Resuspension of soil contaminated as a result of secondary processes is considered in conjunction with the intruder and general public protection objectives.

Federal, State, and Local Groundwater Protection Standards. The general philosophy underlying groundwater protection standards assumes that protecting groundwater quality to drinking-water standards will preserve the groundwater for existing and future beneficial uses. The DOE-RL 5820.2A objective of 4 mrem/yr for all radionuclides via the drinking-water pathway is generally consistent with, or more protective than, the federal standards for radionuclides in public drinking-water systems (40 CFR parts 141 and 143). Existing and proposed drinking-water standards apply the 4-mrem/yr dose limit to beta- and photon-emitting radionuclides, and they include separate concentration limits for alpha emitters. Inclusion of all radionuclides in the 4-mrem/yr performance objective should therefore provide a more conservative approach. It is also consistent with groundwater protection requirements in regulations being developed by the U.S. Environmental Protection Agency (EPA) for disposal of radioactive waste (proposed amendment to 40 CFR 191; see 58 FR 7924) and EPA's proposed draft of 40 CFR 193 (as discussed in Gruhlke, Galpin and Holcomb 1989).

RCRA (40 CFR 264 and 40 CFR 265) and State of Washington Dangerous Waste Regulations (WAC 173-303). These regulations apply to management of nonradiological hazardous waste, including standards for final disposal of solid waste. They include requirements for construction, operation, and closure of land disposal facilities and provide for monitoring of leachate and groundwater over a limited period of time (typically 30 years after closure). The groundwater protection requirements for inorganic hazardous constituents specified in these standards are generally consistent with, but less comprehensive than, the corresponding drinking-water standards. DOE has applied for a Part B Dangerous Waste Permit under WAC 173-303, approval of which will demonstrate that the Grout Disposal Facility meets the requirements of that regulation. They will not be addressed further in this performance assessment.

Time of Compliance. Except for DOE-RL Order 5820.2A, the applicable DOE Orders and other standards do not specify the time period over which the various performance objectives apply to radioactive waste disposal. In general, the guidance in DOE-RL Order 5820.2A, along with design goals for the Grout Disposal Facility, will be used to evaluate the results of this analysis. Consistent with DOE-RL Order 5820.2A, the ALARA requirement for collective dose estimates is evaluated at the time of peak dose; whenever the peak occurs.

The general public protection and groundwater protection requirements are evaluated for regulatory compliance at 1,000 years, and they are also compared to the programmatic design goal for the Grout Disposal Facility at 10,000 years. The 10,000-year evaluation period for waste disposal activities is based on historical precedent in the HDWEIS (U.S. DOE 1987) and the performance assessment completed prior to disposal of grouted PSW (Sewart et al. 1987). It is also consistent with the compliance time specified in proposed EPA regulations for high-level radioactive waste disposal (58 FR 7924).

The requirements for intruder doses following either a single or continuous exposure are evaluated at 500 years after disposal because passive controls in the form of an intrusion barrier and markers are included in the disposal system design. The incorporation of passive controls to deter intruders for up to 500 years is required by DOE-RL Order 5820.2A where the waste may remain hazardous beyond the assumed institutional control period (otherwise defined as 100 years). Evaluation of intruder doses at

500 years is also consistent with practices established by the U.S. Nuclear Regulatory Commission for commercial radioactive waste disposal facilities that incorporate passive controls (10 CFR 61).

1.5.2 Performance Objectives and Scenarios for the Grout Disposal Facility

Specific performance objectives have been established for this performance assessment based on the regulatory requirements discussed in the previous section. The performance objectives address the required elements listed in DOE Order 5820.2A and DOE-RL 5820.2A, including public protection, compliance with the Clean Air Act, ALARA, intruder protection, and groundwater protection. The ability to meet these requirements is evaluated by means of several different transport and exposure scenarios that are described briefly in this section (see Section 3.2 and Appendix M for a complete description). In conducting the analysis, the potential impacts of effluents from the Grout Disposal Facility are evaluated and reported for a period of time sufficient to determine the maximum dose associated with each scenario. However, for purposes of determining whether the performance objectives are met, the time of compliance is as stated for each objective. Each scenario is evaluated independently of the others, although there may be a small probability that two or more scenarios could interact (for example, intrusion and use of groundwater).

Performance Objective for General Public Protection. The public protection requirement in DOE-RL Order 5820.2A that specifies a maximum dose of 25 mrem/yr to an individual member of the public via all pathways is adopted as the primary performance objective for this assessment. The disposal system's performance is evaluated at 1,000 and 10,000 years using three separate scenarios that represent different transport and exposure conditions. A fourth scenario assesses the potential impact of natural events on the Grout Disposal Facility. The general public protection scenarios include all credible exposure pathways, including ingestion of locally produced food, ingestion of drinking water (well scenarios only), inadvertent ingestion of contaminated soil, inhalation of resuspended soil, and external exposure to the contaminated ground surface.

Two scenarios involve use of groundwater downgradient from the disposal facility for domestic purposes and for irrigation of either a home garden or a 2-hectare (5-acre) family farm. The garden scenario assumes a relatively low food production rate and a higher groundwater concentration because of the smaller quantity of water required to maintain the garden as compared to a farm. In the garden scenario, the leachate plume from the Grout Disposal Facility is mixed in the aquifer at a depth corresponding to the screened interval of a monitoring well, and no other dilution by pumping of clean water is assumed. The farm scenario results in a higher onsite food production; however, the quantity of water needed to maintain the farm requires a higher pumping rate, which results in dilution of the contaminated groundwater plume with clean water from the aquifer. The well for both scenarios is assumed to be no farther than 100 m from the boundary of the disposal site.

Two additional scenarios assess the impact of soil contamination from the direct upward diffusion of waste components from the Grout Disposal Facility, or from disruption of the disposal facility by natural forces in the form of a catastrophic flood. Unlike the groundwater and upward diffusion scenarios, the

flood scenario is evaluated at 50,000 years after disposal because that is the earliest predicted time frame for recurrence of severe flooding that could potentially disturb the disposal site.

Performance Objective for Groundwater Protection. The performance objective for groundwater protection in this performance assessment consists of the 4-mrem/yr maximum dose to an individual exposed via the drinking-water pathway only from DOE-RL Order 5820.2A. In this case, the dose is estimated for an individual consuming 2 L/d of water from a downgradient well located 100 m from the disposal site boundary. The groundwater concentrations were assumed to be the same as those in the garden scenario, based on minimum pumping rate at a downgradient well. This objective is also evaluated at 1,000 years and 10,000 years after disposal.

For nonradioactive waste components, the groundwater concentrations are compared at 1,000 and 10,000 years with the most restrictive concentration limits listed in the state and federal drinking-water standard. The standards for individual chemical species are listed with the results of the groundwater transport analyses in Chapter 4. This evaluation is provided for information to complete the groundwater analysis, although the performance assessment is concerned primarily with radionuclides in the waste.

Performance Objectives for Intruder Protection. The performance objectives for intruder protection in this performance assessment are a maximum single acute dose of 500 mrem, or a continuous dose of 100 mrem/yr, to a person who inadvertently intrudes into the disposal site, consistent with DOE Order 5820.2A and DOE-RL 5820.2A. Both objectives are evaluated at 500 years or more after disposal. The scenario associated with the acute exposure objective involves drilling a well directly through a disposal vault, and estimates the dose to a worker who operates the drilling apparatus. External exposure is the major pathway considered in this scenario, although inadvertent ingestion and inhalation of contaminated soil that is brought to the surface are included as well. The 100-mrem/yr objective for continuous exposure is applied to an individual who resides at the drilling site following completion of the well. The pathways evaluated in this scenario are similar to those for the general public protection scenarios, except that ingestion of contaminated groundwater is not considered.

Performance Objectives for Compliance With Clean Air Act. The 40 CFR 61, Subpart Q standard of 20 pCi/m²-s for radon emissions from DOE storage and disposal facilities is adopted as the performance objective for Clean Air Act compliance in this performance assessment. This objective is assessed at a time corresponding to the maximum emission rate.

Performance Objectives for ALARA. As defined in DOE Order 5400.5, ALARA is not a quantitative standard but a process by which facilities demonstrate that they are restricting their radioactive effluents to a level that is as low as practical. DOE-RL Order 5820.2A defines ALARA in terms of collective dose (and therefore overall risk), and the 500 person-rem/yr performance objective is applied to the estimated dose for two scenarios in this performance assessment. Both scenarios are evaluated at the time of maximum collective dose.

The dose to a population of 5,000,000 people living along the Columbia River downstream from Hanford is estimated based on an all-pathways scenario similar to that used for the individual public protection objective. The major difference is that domestic and irrigation water is obtained from the river, and pathways related to recreational use of the river and consumption of fish are also included.

The collective dose resulting from use of groundwater via a community well is also estimated for comparison with the ALARA objective. This dose is expected to be somewhat higher than the collective dose for the river scenario because of the degree to which effluents from the Grout Disposal Facility are diluted in the river. The collective dose is estimated based on the irrigated garden dose to an individual as described for the general public protection objective. The peak dose in that scenario is multiplied by a population of 80 people to obtain an estimate of the potential collective dose resulting from the use of groundwater. A population of 80 represents the maximum number of people that could be supported by the contaminated groundwater plume at the lower pumping rate applied to the garden scenario. The water usage rates in this scenario are based on domestic requirements plus irrigation of a 10-m x 10-m garden for every four people. Use of groundwater to supply the domestic needs of a larger population would result in substantial dilution of contaminated groundwater by clean water from the aquifer; therefore, use of the 80-person population maximizes collective dose in this scenario.

1.6 Structure of This Performance Assessment

This performance assessment is organized according to the format recommended by the Oversight and Peer Review Panel for performance assessments (Case et al. 1989). Chapter 1 discussed the general scope and methods used in the performance assessment, along with applicable regulatory guidance used to develop performance objectives for the disposal system. Chapter 2 describes the Grout Disposal Facility and its environment, characteristics of the waste, and the grout disposal system. Chapter 3 discusses the methods used to assess performance of the system, including the radionuclide transport pathways and exposure scenarios, assumptions used in modeling system performance, and quality assurance procedures. Chapter 4 presents and integrates results from the transport and exposure models used to estimate the potential consequences of effluents from the grout disposal vaults. Chapter 5 interprets disposal facility performance with respect to the performance objectives defined in Chapter 1. Chapter 6 contains brief resumes of contributors to the document, and Chapter 7 lists the cited references. The appendices provide additional detailed information about topics presented in the main text. The last appendix, Appendix R, provides responses to questions raised by a formal DOE/Headquarters Peer Review Panel from February through September 1994, plus the Panel's final recommendations regarding their review of the performance assessment process.

2.0 Disposal Facility Description

Grout is a waste form prepared by combining low-level liquid waste with a mixture of dry, cementitious materials to form a slurry that solidifies by hydration reactions, producing a solid monolith that contains the hazardous constituents. The Grout Treatment Facility, located in the 200 East Area of the Hanford Site, consists of four components to receive liquid waste, prepare the grout slurry, and pump the slurry into reinforced-concrete vaults where it solidifies. The four facility components are 1) the Dry Materials Facility, which stores and distributes the dry cementitious materials; 2) the Feed Transfer System, which delivers the waste liquids to 3) the Grout Processing Facility, where the slurry is prepared from the liquid and solid materials; and 4) the Grout Disposal Facility, which consists of a group of underground concrete vaults that receive the slurry. In the Grout Disposal Facility the slurry solidifies to form a large monolithic solid. Each of the concrete vaults in the facility will be surrounded by a 1-m- (40-in.-) thick asphalt barrier. About 122 million liters (32 million gallons) of waste will be grouted for disposal in about 33 vaults. The disposal area for all the vaults in the facility is about 430 m (1,408 ft) by 208 m (682 ft). The vaults will be covered by additional barriers to reduce and redirect infiltrating water away from the vaults.

This chapter includes a description of the Hanford Site and its relationship to the Grout Disposal Facility site to identify the geohydrologic characteristics needed to model contaminant flow and transport at the facility, and to identify possible transport and exposure pathways. Also included is a detailed description of the inventory of waste to be disposed, along with details of the Grout Disposal Facility and vaults that are used to develop a conceptual model of the engineered disposal system.

To develop a reasonable, site-specific contaminant flow and transport model to evaluate the long-term mobility of radioactive and hazardous material releases from the Grout Disposal Facility, knowledge of hydraulic and contaminant mobility properties of the engineered system and disposal site is required. Furthermore, properties used in modeling must be selected on the basis of actual material properties, or justified by comparing with similar materials. Guidelines for considering these properties are established in *Performance Assessment Review Guide for DOE Low-Level Waste Disposal Facilities*, DOE/LLW-93 (Dodge et al. 1991). These guidelines recommend a description of site characteristics, an inventory estimate, and a waste form processing and disposal description. These descriptions provide needed background information and the hydraulic and material properties required for model calculations. The site characteristics section emphasizes factors that may influence contaminant mobility and discusses their use in modeling. Inventory estimates and uncertainty are considered for subsequent application to dose calculations, and the engineered system is described to develop model constraints and boundaries.

This chapter provides general descriptions of the Hanford region and grout disposal site, the wastes to be grouted and the grout waste form itself, and the grout processing and disposal facilities. Chapter 3 then develops the conceptual descriptions of the release of radionuclides from the grout and the subsequent pathways leading to exposures to the public.

2.1 Site Characteristics: Hanford Site and Grout Disposal Site

This section describes the Hanford Site and Grout Disposal Facility, including both local and regional features that may influence the facility environment or be impacted by the facility operations. The Grout Disposal Facility is located within the Hanford Site area, so many regional characteristics are common to both the facility and much of the Hanford Site area. These include climate, some aspects of vadose zone lithology and hydrologic properties, and ecology. Accordingly, Hanford Site characteristics that are required to understand the more local Grout Disposal Facility characteristics are discussed along with the facility features. This information is then used in later chapters to support development of conceptual models for flow and transport calculations, to define certain parameters and boundary conditions, to determine exposure scenarios, and to help provide a basis for interpreting results. Cultural geography and demography are discussed first, followed by the physical geography, including topography/physiography, natural resources, and land/water uses. Ecology, climate, and meteorology as they relate to possible contaminant pathways caused by plants and animals, and changes in Site hydrology caused by climate, are discussed. The section concludes with descriptions of the geologic and hydrologic setting, current monitoring of groundwater contamination and estimates of background radiation, and Hanford Site seismic activity.

2.1.1 Site Location and Cultural Geography

The Hanford Site is a 1,450-km² (560-mi²) area of semiarid land located in the southeastern part of Washington State. It is owned by the U.S. Government and restricted to U.S. Department of Energy (DOE) operations or activities approved by DOE. Figure 2.1 shows the Hanford Site with respect to Washington State while Figure 2.2 depicts the Site in more detail in relation to southeastern Washington roads, river systems, and counties. Figure 2.3 shows the road systems and operational areas of the Site itself. As shown in Figure 2.3, the Grout Disposal Facility is located near the central portion of the Hanford Site adjacent to an operational area designated the 200 East Area.

Figure 2.1 shows the principal cities and towns in the extended regional area of the Hanford Site and indicates that the major metropolitan areas such as Spokane and Seattle, Washington, and Portland, Oregon are all located more than 160 km (100 mi) from the Site. Note in Figure 2.2 that the Hanford Site is located within three counties--Benton, Franklin, and Grant--with the largest area in Benton County. The major river systems (see Figures 2.1 and 2.2) are dominated by the Columbia River, which flows through the Hanford Site from the northwest corner flowing eastward then turns and flows south, forming part of the eastern border of the Site just north of Richland, Washington. The Yakima River is south of the Site and flows from west to east, entering the Columbia River near the towns of Richland, Kennewick, and Pasco (the Tri-Cities). The Snake River, with a discharge second only to the Columbia River in this area, enters the Columbia River just south of the Tri-Cities. The Columbia River, as well as the Snake and Yakima rivers, are used for many purposes including irrigation and drinking-water consumption. The Columbia River is navigable to barge traffic up to the southeastern part of the Hanford Site. All major rivers in the vicinity of the Hanford Site flow into the Columbia which, while having a

S9211085.21

Figure 2.1. Hanford Site in Washington State

considerably high discharge volume, also supports a large industrial, agricultural, and population base and is considered a major pathway for contaminant impacts. The Columbia River, at its nearest point, is about 9.7 km (6 mi) from the Grout Treatment Facility.

Public highway access to the Hanford Site is shown in Figure 2.3 with highway access controlled at two locations. These are the Yakima Barricade in the northwest part of the Site and the Wye Barricade in the southeastern part of the site north of Richland (see Figure 2.3). State Highway 240 with unrestricted public access passes through the Hanford Site via a right-of-way separated from the Site by a fence. This highway passes within 8 km (5 mi) of the Grout Treatment Facility. To the west of Highway 240, but still on the Hanford Site, is the Arid Lands Ecology Reserve. North of the Columbia River, also on the Site, is a wildlife reservation. Both are unpopulated. The nearest population center to the Grout Treatment Facility is about 48 km (30 mi) away at Richland, Washington.

S9211085.23

Figure 2.2. Hanford Site, Counties, and the Regional Highway Network

The major activities at the Hanford Site that generated radioactive and hazardous waste products were the plutonium-production reactors located along the Columbia River in areas designated the 100 Areas and the chemical processing areas near the central part of the Hanford Site designated the 200 Areas (see Figures 2.3 and 2.4). The 200 Areas contain the large underground tanks that are the source of feed stock for the Grout Treatment Facility. Some sites near the 200 Areas have been leased for disposal of commercial low-level waste. A summary of some of these activities dating back to the 1940s is described below because they are considered a major source of background radiation levels and groundwater baseline concentrations.

In 1943, the U.S. Army Corps of Engineers selected the Hanford Site for the construction of facilities to produce nuclear weapon materials for the war effort. Major programs at the Hanford Site, presently managed by the DOE, are dedicated to waste management, environmental restoration, research and

Figure 2.3. Hanford Site Map Showing Public Highways

Figure 2.4. Activities at the Hanford Site 200 East and 200 West Area

development, and technology development. The DOE nuclear facilities occupy about 6% of the total available area. Hanford Site operating areas, as shown in Figure 2.3, are identified by numbers. The six 100 Areas bordering directly on the Columbia River in the northern portion of the Hanford Site contain nine graphite-moderated plutonium production reactors. Eight of these reactors were shut down by the early 1970s. The ninth is the N Reactor, which became operational in 1963 and was the first dual-purpose reactor built in the United States. The N Reactor was operational until 1986 and is currently in cold standby status.

The Fast Flux Test Facility (FFTF), a liquid-metal cooled fast reactor previously used for testing breeder reactor fuels, materials, and components, is located in the 400 Area. The FFTF was operational until 1992 and is currently in standby status. In previous years, the 300 Area was dedicated to the fabrication fuel for the N Reactor and other reactors on the Hanford Site. Now, the 300 Area is used for research programs performed in laboratories constructed over the last 30 years.

A 3.9-km² (1.5-mi²) parcel of land located between the 200 West and 200 East Areas is leased to the State of Washington. A portion of this land is subleased to U.S. Ecology, Inc., a private company, for the disposal of commercially generated low-level radioactive waste. An additional 2.6-km² (1.0-mi²) parcel has been transferred to the State of Washington as a potential site for a nonradioactive hazardous waste disposal site. A 4.4-km² (1.7-mi²) parcel of land is leased to the Washington Public Power Supply System for commercial nuclear power reactors. The Washington Nuclear Plant (WNP-2), a boiling-water reactor, is currently the only nuclear reactor in operation on the Hanford Site. Completion of construction has been deferred on WNP-1 and terminated on WNP-4; both reactors are pressurized-water reactors.

Activities associated with fuel reprocessing; plutonium and uranium separation; plutonium finishing; and waste management, storage, and disposal were conducted in the 200 Areas. Wastes from research and development activities in the 300 Area and other programs in the 100 Area also are sent to the 200 Areas for storage and/or disposal. Also, the FFTF (400 Area) ships radioactive waste to the 200 Area. The facilities dealing with these activities are located near the center of the Hanford Site as shown in Figure 2.4. The 200 Areas are currently bounded by security fences.

The location of chemical processing facilities, waste disposal trenches, waste burial grounds, and tank farms in the 200 East Area is shown in detail in Figure 2.5. The Grout Treatment Facility is located on the eastern border of the 200 East Area, with the Grout Processing Facility in proximity to the feed tank transfer system and the Grout Disposal Facility containing the individual grout vaults just outside of the 200 East Area. The Grout Processing Facility is about 607 m (2,000 ft) east of the Plutonium-Uranium Extraction (PUREX) Plant, which formerly processed spent reactor fuel and is now being shut down, and about 429 m (1,407 ft) south of the 242-A Evaporator, which will generate part of the waste to be grouted. The 242-A Evaporator is the closest facility to the Grout Processing Facility. The closest tank farm is the 241-AP farm to the west of the facility. The Grout Disposal Facility, the focus of this performance assessment, shows the approximate location of the grout vaults. The Grout Treatment Facility encompasses about 100 hectares (0.4 mi²) and is shown in an aerial view in Figures 2.6 and 2.27, along with the initial construction stages of the first four vaults for disposal of double-shell tank wastes. Figure 2.5 also shows the 216-B evaporation ponds to the northeast of the Grout Disposal Facility. These ponds are currently in operation and contribute to the net recharge in the vicinity of the facility, resulting in a slight elevation of the water table. All chemical processing activities and use of the 216-B ponds are to be stopped and the area cleaned up in approximately 30 years. Consequently, the conceptual model evaluated in this performance assessment includes a lower water table consistent with no recharge contribution from the ponds.

2.1.2 Demography

The population distribution surrounding the Hanford Site provides a basis for evaluating potential contaminant release impacts and effects of various exposure pathways, and forms the basis for projecting future population changes.

The major population centers within an 80-km (50-mi) radius of the Hanford Site are illustrated in Figure 2.7 along with populations based on the 1990 U.S. Bureau of Census estimates (U.S. Department of Commerce 1991). The Tri-Cities area of Richland, Kennewick, Pasco, and West Richland lies southeast of the Hanford Site and is both the largest population center and the center closest to the Site. Other major population centers include Yakima and the Yakima Valley towns to the west, Umatilla to the south, and Moses Lake to the north. The cities of Ellensburg and Walla Walla lie just beyond the 80-km (50-mi) radius. Portions of Benton, Franklin, Adams, Grant, Kittitas, Yakima, Klickitat, Walla Walla, Morrow, and Umatilla counties are included in the 80-km (50-mi) radius centered on the Hanford Meteorology Station (HMS), located between the 200 East and 200 West Areas.

Figure 2.5. Location of the Grout Treatment Facility in the 200 East Area

Figure 2.6. Aerial View of the Grout Treatment Facility Looking West (Construction is now complete on the next four vaults to be filled, Vaults 102, 103, 104, and 105.)

Note: If population not listed, less than 1,000

HMS = Hanford Meteorological Station

S9108042.1

Figure 2.7. Population Centers Within 80-km Radius of the Hanford Site

Based on the 1990 census (U.S. Department of Commerce 1991) as summarized in Cushing (1991), the population in Benton County was approximately 112,000, with an approximate population in unincorporated portions of the county of 28,000. Of the remaining population, approximately 32,000 people reside in Richland; 42,000 people reside in Kennewick; and 10,000 people reside in West Richland, Benton City, and Prosser. In 1990, the population of Franklin County was approximately 37,000, with

20,000 people living in Pasco, 2,400 people living in other incorporated areas, and 15,000 people living in unincorporated areas. During 1990, Benton and Franklin Counties accounted for approximately 3% of the population in Washington State.

Based on estimates made during the 1970 and 1980 census years, the population in the area grew approximately 55% (Watson et al. 1984). This population growth and subsequent decline in 1982 were attributed to the creation and loss of several thousand construction jobs at the Washington Public Power Supply System power reactors. Watson et al. (1984) projected that the populations within a 16-km (10-mi) radius, primarily reflecting the Tri-Cities, would increase by 94% between 1980 and 2030 and that the population between 16 and 80 km (10 and 50 mi) would increase by 55%.

The socioeconomics of the area surrounding the Hanford Site are described in Appendix A. The major employment sectors in the Tri-Cities area since 1970 have been the DOE and its Hanford contractors; the Washington Public Power Supply System, which operates a nuclear power plant; agriculture and a large food-processing industry; plus several smaller industrial operations. Exclusive of the DOE, agriculture and food processing are the dominant industries. Accordingly, this performance assessment considers a scenario in which the 200 Areas will be used for a small farm and garden after decommissioning and cleanup. Although large irrigated agricultural operations currently exist east of the Hanford Site, water rights restrictions may limit future expansion. Recently an evaluation was completed to consider additional possible future uses of the Hanford Site (Hanford Site Working Group 1992).

No major mining operations exist in the Hanford Site area other than some local gravel processing, but oil and gas exploration has occurred. These activities have been primarily exploratory in nature and no production has resulted.

2.1.3 Topography and Physiography

The topographic and physiographic conditions can influence local climate at the Hanford Site, in turn affecting features such as vegetation, sand dune formation and mobility, and local wind directions. These features are major contributors in controlling the net groundwater recharge rates that are significant parameters in evaluating contaminant flow and transport processes. In addition, surface drainage pathways are largely determined by topographic features. Some features significant to the Hanford Site and the Grout Disposal Facility are discussed below.

The physical setting of the Hanford Site has been characterized extensively during past activities at the Site. These activities include the siting of nuclear reactors, characterization activities for the Basalt Waste Isolation Project (BWIP), and waste management activities. A summary of the Site topography and physiography is given below; more detailed discussions of the regional setting and the Site are given in U.S. DOE (1987, 1988c), Myers et al. (1979), Meyers and Price (1981), and Reidel and Hooper (1989).

The Hanford Site is situated within the Pasco Basin of south-central Washington (Figure 2.8). The Pasco Basin is one of many topographic depressions located within the Columbia Plateau Physiographic Province (Figure 2.9), a broad basin located between the Cascade Range and the Rocky Mountains. The Columbia Intermontane Province is the product of Miocene continental flood basalt volcanism and regional deformation that occurred 13 to 25 million years ago. The Pasco Basin is bounded on the north by the Saddle Mountains; on the west by Umtanum Ridge, Yakima Ridge, and the Rattlesnake Hills; on the south by Rattlesnake Mountain and the Rattlesnake Hills; and on the east by the Palouse Slope (see Figure 2.8).

The physiography of the Hanford Site is dominated by the low-relief plains of the Central Plains physiographic region and anticlinal ridges of the Yakima Folds physiographic region (Figure 2.10). Surface topography at the Site is the result of 1) uplift of anticlinal ridges, 2) Pleistocene cataclysmic flooding, 3) Holocene eolian activity, and 4) landslides. Uplift of the ridges began in the Miocene epoch and continues to the present. This uplift is occurring on geologic time scales (i.e., over tens of millions of years) and is not incorporated into our conceptual model of the Grout Disposal Facility, which addresses a time scale of tens of thousands of years. Cataclysmic flooding occurred when ice dams in western Montana and northern Idaho were breached, allowing large volumes of water to spill across eastern and central Washington. The last major flood occurred about 13,000 years ago, during the late Pleistocene Epoch. Anastomosing flood channels, giant current ripples, bermounds, and giant flood bars are among the landforms created by the floods. These formations resulted in heterogeneous and discontinuous characteristics for sediments ranging in size from silts to coarse gravels that yield a wide range of vadose zone hydraulic properties. Since the end of the Pleistocene, winds have locally reworked the flood sediments, depositing dune sands in the lower elevation and loess (very fine wind-blown silts) around the margins of the Pasco Basin. Generally, sand dunes have been stabilized by anchoring vegetation except where they have been reactivated where vegetation has been disturbed. Most sand dunes are located southeast of the grout site and are stabilized by vegetation (see Figure 2.10).

The 200 Areas that include the Grout Treatment Facility are situated on a broad flat area called the 200 Areas plateau. The 200 Areas plateau is near the center of the Hanford Site at an elevation of approximately 198 m (650 ft) to 229 m (750 ft) above mean sea level. The plateau decreases in elevation to the north, northwest, and east toward the Columbia River, and plateau escarpments have elevation changes of between 15 m (50 ft) to 30 m (100 ft). Previous landslide activity in the area is generally limited to the White Bluffs area east of the Site and the Rattlesnake Hills south of the Site. No landslide activity is observed in the vicinity of the 200 Area plateau.

The location of the Hanford Site and Grout Disposal Facility in an intermontane basin helps maintain a semiarid climate with low recharge. Most topographical surface features such as sand dunes and landslides that could disturb the near-surface hydraulic characteristics impacting recharge are not located at the Grout Disposal Facility. Moreover, sand dunes are indicators of past, cumulative wind directions, so their location approximately downwind of the Grout Disposal Facility suggests that future dune formation over the facility is not likely.

Figure 2.8. Geologic Structures of the Pasco Basin and the Hanford Site

Figure 2.9. Divisions of the Columbia Intermontane Province and Adjacent Snake River Plains Province

2.1.4 Ecology

This section summarizes the ecology of the Hanford Site, with emphasis on plant and animal activities that may impact exposure pathways through root penetration and burrowing through barriers into vaults. Secondly, the types of plants and animals and their density can affect net groundwater recharge, which is highly influenced by surface vegetation and burrowing. A detailed description of the ecology of the Hanford Site is given in Appendix D, which summarizes the evaluation presented in Cushing (1991). The Cushing document details both the terrestrial and aquatic ecology of the Hanford Site and presents extensive listings of plant and animal species.

The Hanford Site is botanically characterized as a shrub-steppe environment and contains numerous plant and animal species adapted to the region's semiarid environment. Because of the aridity and low water-holding capacity of the soils, the productivity of both plants and animals is relatively low. The site consists of mostly undeveloped land with only about 6% of the area occupied by chemical processing facilities, nuclear reactors that no longer operate, or supporting facilities. The activities do not have a significant impact on the Site ecology. Most of the Hanford Site has not experienced tillage or agriculture grazing since the early 1940s. This summary will consider only terrestrial ecological impacts because the Grout Disposal Facility is not located in the vicinity of significant aquatic ecological systems. All aquatic

S9211085.43

Figure 2.10. Landforms of the Pasco Basin and the Hanford Site

sites in the 200 Areas are temporary water bodies associated with waste disposal practices. Refer to Appendix D for a more detailed description of these and other aquatic sites at the Hanford Site.

The dominant plants in the area in the early 1800s before settlement and agricultural activities were big sagebrush and perennial bunchgrass. Agriculture opened the area to invasion of alien plants, namely cheatgrass. Cheatgrass today is dominant on fields and rangeland that were cultivated 40 years ago. The dominant plants on the 200 Area Plateau are big sagebrush, rabbitbrush, cheatgrass, and Sandberg's bluegrass, with cheatgrass providing half the total plant cover. Root penetration to depths of over several meters has not been demonstrated in the 200 Areas (Cushing 1991). Rabbitbrush roots have been found at a depth of 2.4 m (8 ft) near the 200 Areas.

The most abundant nesting birds of the shrub-steppe at the Hanford Site are the horned lark and western meadowlark, but significant populations of chukar and gray partridge are supported. Mourning doves also nest throughout the Site. The most abundant mammals of the Site are mice, ground squirrels, gophers, voles, and cottontail rabbits. Larger animals include mule deer and elk. The coyote is the principal mammalian predator at the Site.

The top of the grout vaults will be about 5 m (16.4 ft) or more below grade and the grout waste form will be below this level, such that the system is well below the soil root zone and below possible burrowing animal depths, and covered by at least two barrier systems. The permanent isolation barrier to be constructed at the surface that will cover all vaults also is designed to inhibit both root penetration and burrowing animals. Occasional range fires occur in the area, but these have only a short-term impact because natural vegetation quickly returns within a year or two. Consequently, the long-term impact to exposure pathways from short-term ecological variability has not been considered in this performance assessment.

2.1.5 Climate and Meteorology

Consideration of local and regional climate patterns and future climate projections is required to evaluate the impacts on groundwater recharge and flood potential. Total precipitation and seasonal frequency has a direct influence on water available for recharge and a secondary influence on recharge through effects on vegetation. In evaluating contaminant flow and transport, the recharge rate is a primary parameter in model simulations. A projection of potential long-term climate conditions is required to evaluate possible future changes in climate that might result in higher precipitation rates or glaciation. A general description of modern climate patterns in the regional Hanford Site area and climate patterns of the recent past are summarized in this section, along with possible future changes. A more detailed discussion of climatology related to the Hanford Site is given in Appendix B.

The climate of the Pasco Basin can be classified as midlatitude semiarid or midlatitude desert, depending on the climatological classification scheme being used. Summers are warm and dry with abundant sunshine. Large diurnal temperature variations are common during this season, resulting from intense solar heating and nighttime cooling. Daytime high temperature in June, July, and August can

exceed 40°C (104°F). Winters are cool with occasional precipitation. Outbreaks of cold air associated with modified arctic air masses can reach the area and cause temperatures to drop below -18°C (0°F). Overcast skies and fog occur periodically during winter.

2.1.5.1 Modern Climatic Patterns

The Pasco Basin is in the rain shadow of the Cascade Range. These mountains limit much of the maritime influence of the Pacific Ocean, producing a climate that is more continental in nature than would occur if the mountains were not there. The local topographic features have a significant effect on temperature, wind, and precipitation because all air masses that reach the Pasco Basin undergo some modification following their passage over the relatively complex topography of the area. The climate of the Hanford Site within the Pasco Basin is greatly influenced by the Cascade Mountains beyond Yakima to the west. In addition to providing a rain shadow effect, this range also serves as a source of cold air drainage, producing a considerable effect on the wind regime at the Hanford Site.

Climatological data are available from the Hanford Meteorological Station (HMS), located between the 200 East and 200 West Areas and situated on a plateau at about 215 m (705 ft) elevation. Data have been collected at this location since 1945. Temperature and precipitation data are also available from nearby locations for the period 1912 through 1943. A data summary through 1980 has been published by Stone et al. (1983). Data from the HMS are representative of the general climatic conditions for the region and describe the specific climate of the 200 Area plateau, including the Grout Disposal Facility. Local variations in the topography of the Hanford Site may cause some aspects of climate at portions of the Hanford Site to differ significantly from those at the HMS. For example, winds near the Columbia River are different than those at the HMS. Similarly, precipitation along the slopes of the Rattlesnake Hills differs climatically from that at the HMS.

Temperature. Diurnal and monthly averages and extremes of temperature are presented in Stone et al. (1983). Average monthly temperature at the HMS is 12°C (54°F). The unusually cool nights that do occur result from cool gravity winds originating from the Cascade Mountains. Temperatures at the Hanford Site are colder in the winter and warmer in the summer than would be the case without the Cascades blocking the more equitable maritime climate to the west. The Pasco Basin is warmer during the winter than a site at an equivalent latitude on the Great Plains in the midcontinent because mountain ranges to the north and east shield the area from many of the arctic surges that descend out of Canada. Half of all winters are free of temperatures of -18°C (0°F) or lower. Additional details on daily and seasonal temperature fluctuations are given in Appendix B.

Precipitation. Measurements of precipitation have been made at the HMS since 1945. Average annual precipitation at the HMS is 16 cm (6.2 in.). The 3 months of November through January contribute 44% of this total, while the 3 months of July through September contribute only 13%. On the average there are only two occurrences per year of 24-hour amounts of precipitation of 1.27 cm (0.5 in.) or more. Rainfall intensities of 1.27 cm/h persisting for 1 hour are expected once every 10 years. Only two occurrences of 24-hour amounts of precipitation of 5.08 cm (2 in.) or more have been recorded in the entire

35 years of record (1946 through 1980). One of these was the record storm of October 1-2, 1957, in which rainfall totalled 2.74 cm in 3 hours, 4.27 cm in 6 hours, and 4.78 cm in 12 hours.

About 38% of all precipitation during the months of December through February is in the form of snow. Winter monthly average snowfall ranges from 0.8 cm (0.3 in.) in March to 13.5 cm (5.3 in.) in January. Only one winter in four is expected to accumulate as much as 15.24 cm (6 in.) of snow on the ground. On average, four seasonal number days have 15.24 cm or more of snow on the ground, although the 1964-1965 winter had 35 days with snow on the ground, 32 of which were consecutive. That winter also provided one of the greatest snow depths, with 30.7 cm (12 in.) of snow occurring in December 1964. The record greatest depth of snow on the ground is 62.2 cm (24.5 in.) in February 1916. This precipitation profile suggests opportunities for a nonzero infiltration center around the direction and frequency of precipitation events during the winter months when evaporation is less and plant uptake and transpiration is maintained.

2.1.5.2 Climate Pattern of the Recent Past

Cropper and Fritts (1986) derived a 360-year regional reconstruction of seasonal and annual variations in temperature and precipitation from statistical relationships between meteorological records from Columbia Basin stations and tree-ring data from western North America. They calibrated the relationship between Columbia Basin weather records and a network of 65 tree-ring chronologies. The results suggest that the average temperature of the Columbia Basin for the last three centuries was slightly higher (0.09°C [0.16°F]) and more variable (4% higher standard deviation) than in the 20th century. The increase was primarily attributed to warmer winters. The reconstructions also suggest that the last three centuries were wetter on the average (0.81 cm [0.31 in.]), primarily in the autumn. Furthermore, droughts were apparently more frequent starting in the second half of the 17th century and lasted longer than droughts of the 20th century.

Gramulich (1987) also used multiple regression models to reconstruct precipitation in the Pacific Northwest. The results indicate that the average precipitation of the 18th and 19th centuries did not differ from the average precipitation of the 20th century. The reconstructions also indicate that extreme drought years, caused by high-pressure ridges shifting storm tracks to the north during normally wet winter months, were common to all regions in the Pacific Northwest.

2.1.5.3 Holocene Paleoclimate Patterns

Chatters (1991) and Chatters and Hoover (1992) summarize proxy evidence for climatic change in the Columbia Basin for the last 10,000 to 13,000 years. Findings identify a terminal Pleistocene environment kept cool and dry by masses of ice and glacial meltwater, supporting a mosaic of now-allopatric plant and animal communities. This was followed between 10,000 and 8,500 years ago by a period of warmer-than-modern summers, colder-than-modern winters and low, but spring-dominant, precipitation, supporting extensive grasslands and the faunas associated with them. By 8,000 years ago, summer and

winter were both relatively warm, and precipitation was at least 33% below modern levels. This climate pattern resulted in reduced stream flows with late spring flow maxima and extensive development of shrub-steppe vegetation throughout most of the region.

Between 4,500 and 3,900 years ago the climate went through a period of transition to wetter and cooler conditions. Rivers flooded frequently and forests expanded into steppe zones. From 3,900 to 2,400 years ago the climate was cool in summer and cold in winter, with winter-dominant precipitation at least 30% above modern amounts. Warmer, drier conditions returned between 2,400 and 2,000 years ago, reducing vegetation density and renewing flooding.

2.1.5.4 Milankovitch Theory of Global Climatic Change

Among climatologists, it is universally accepted that global climates have undergone significant variation in the past, and such natural variations are expected to continue into the future (Crowley and North 1991). According to the Milankovitch theory, the Pleistocene ice ages were caused primarily by changes in the seasonal distribution of incoming radiation associated with orbit variations. Over the last 800,000 years and possibly for as long as the last 2,000,000 years, the earth has experienced many glacial cycles, each about 100,000-years long with a 10,000-year-long interglacial period (Hays, Imbrie, and Shackleton 1976; Kukla 1981; Berger et al. 1984). The last interglacial/glacial cycle started with a 10,000-year-long interglacial period (deep sea core oxygen isotope stage 5e) about 125,000 years ago, which was immediately followed by a rapid growth of global ice sheets beginning at 115,000 years ago. Glacial climate dominated the earth until about 12,000 years ago when continental ice retreated from its most southern extent into what is now the state of Washington. Based on past geophysical evidence, the next glacial period is approaching. An example of temperature changes during a glacial period is that, during the extreme of the full glacial period about 18,000 years ago, Canada was covered with ice. Temperatures during that period were about 5-10°C (9-18°F) colder than present temperatures.

2.1.5.5 Greenhouse Theory of Climate Change

The potential impact of the increase of some gases in the atmosphere suggests that human activity is contributing to climate change (Hansen et al. 1981; Schneider 1989). The current buildup of carbon dioxide, methane, and other gases from the use of fossil fuels may lead to warming of the lower atmosphere through a process called the "greenhouse effect." The greenhouse effect is not entirely bad. Without greenhouse gases to help blanket the earth and hold heat, this globe would be 24°C (54°F) colder. The concern is based on the apparent rapid increase of carbon dioxide in the atmosphere since 1958, when measurements of carbon dioxide were initiated. Since 1958, carbon dioxide levels have increased 25%. If the levels continue to increase at that rate, the concentration of carbon dioxide will be doubled from the estimated pre-industrial level by the middle of the next century. Complex computer models suggest that global temperature also will increase, with estimates of temperature increases ranging from 1.5°C (3.4°F) to 4°C (9°F) (Houghton, Jenkins and Ephraums 1990).

2.1.5.6 Long-Term Future Climate Change

Although the potential for future warming from the greenhouse effect exists, ultimately the effect will be overwhelmed as the next ice age advances. Berger et al. (1991) review seven models of different complexity developed to predict the global climate for the next 10,000 to 100,000 years (e.g., Calder 1974; Petersen and Larsen 1978; Melice and Berger 1989; Imbrie and Imbrie 1980; Kukla et al. 1981; Berger 1981; Berger et al. 1990). All of the models are in relatively good agreement with the computation of astronomical forcing of climate change. In the absence of anthropogenic disturbances, the long-term cooling trend that began some 6,000 years ago will continue for the next 5,000 years. This first slight minimum will be followed by a stabilization at about 15,000 years, by a cold interval centered at approximately 25,000 years, and finally by a major glaciation at about 55,000 years. If, however, the Greenland ice sheets were to disappear in the next few centuries because of the effects of greenhouse warming, for example, the northern hemisphere ice sheets would not reappear before 15,000 years from now. The climate would remain different from its natural evolution for up to 6,500 years, the maximum ice volume amounting to only two-thirds of its naturally expected size at that time.

Winograd et al. (1992) has questioned the regular cyclic timing used in part to date the pace of the ice ages (e.g., Berger et al. 1991, Hays et al. 1976) by using a well dated and uninterrupted 500,000-year paleotemperature record contained in oxygen-18 concentrations in calcite deposits below the water table in Devils Hole crevasse in Nevada. Rather than a steady beat of ice age-and-interglacial lasting a combined 110,000 years, as predicted by celestial mechanics, Winograd et al. (1992) found that beginning about 420,000 years ago, the ice age-and-interglacials had increasing lengths of 79,000, 85,000, 113,000, and finally 128,000 years, providing an aperiodic swing to the climate cycle. The implication they see for waste isolation is that the present interglacial may last another 10,000 years and continental glacial ice may not reach its maximum extent until 100,000 years.

2.1.5.7 Climate Summary

The analysis of present and future climate conditions at the Hanford Site and in the Site region suggest it is reasonable to assume that climate conditions similar to current conditions will prevail for at least 10,000 years and probably considerably beyond that time. However, considering the uncertainty inherent in any climate analysis, wetter climate conditions and associated higher recharge also will be considered. It is generally accepted that, at some time at about 50,000 years or beyond, major glaciation will occur, followed by possible flooding similar to that following the last glacial stage. Although considerable uncertainty is associated with future glaciation, some simulations in this performance assessment will examine human health impacts associated with a resident population following flooding and redeposition of grouted low-level waste after 50,000 years.

2.1.6 Geology

The geology of the Grout Disposal Facility and the Hanford Site includes thick sequences of water-derived sediments varying in texture from cobbles and coarse gravels to fine silts and clays. These sediments overlay thick basalt flows. An unconfined aquifer exists in the lower part of the sedimentary sequence overlaying the uppermost basalt flow. This aquifer, which is relatively shallow, is considered the primary contaminant pathway for evaluating exposure scenarios because it intercepts infiltration from the vadose (unsaturated) zone above it, thus providing an opportunity for water and contaminant transport to the Columbia River. Knowledge of the thickness and lateral distribution of the sediments and other characteristics is required to define a conceptual model for contaminant transport from the vaults through the vadose zone and from the unconfined aquifer to a well-water user or the Columbia River, to define hydraulic parameters, and to interpret modeling results. The geological and physical setting of the Hanford Site has been extensively characterized during past activities at the Site. This section summarizes the physical geology and environmental setting of the Hanford Site and the facility with emphasis on the sedimentary sequence. A more detailed discussion in Appendix C by Lindberg et al. (1993) presents specific geologic and hydrologic information for the Grout Disposal Facility site. More detailed discussion of the northwest regional geology and the Hanford Site is in U.S. DOE [1987 (Section 4.2 and Appendix O), 1988c], Myers et al. (1979), Meyers and Price (1981), Reidel and Hooper (1989), and Delaney et al. (1991). The hydrology of the Grout Disposal Facility and the Hanford Site is summarized subsequently in Section 2.1.7.

The Hanford Site lies in the Pasco Basin near the eastern limit of the Yakima Fold Belt. The Pasco Basin is a structural depression bounded by anticlinal ridges on the north, west, and south and a monocline on the east (see Figure 2.8). The Pasco Basin is divided by the Gable Mountain anticline into the Wahluke syncline to the north and the Cold Creek syncline to the south. Miocene-aged basalt of the Columbia River Basalt Group and late Miocene to Pleistocene suprabasalt sediments lie beneath the Hanford Site. The basalts and sediments thicken into the Pasco Basin and generally reach maximum thicknesses in the Cold Creek syncline, which is south of the Grout Disposal Facility. Older Cenozoic sedimentary and volcanoclastic rocks underlying the basalts are not exposed at the surface near the Hanford Site. Miocene-aged basalt is exposed at some location, such as Gable Mountain and Gable Butte.

2.1.6.1 Suprabasalt Sediments

Figure 2.11 delineates the general stratigraphy of the suprabasalt sedimentation that makes up the vadose zone sediments beneath the Grout Disposal Facility. This figure is a schematic to illustrate the high degree of heterogeneity and discontinuity in the sediments. The sedimentation is composed largely of Ringold and Hanford formation sediments with the Hanford formation above the Ringold formation. At the Grout Disposal Facility, the Hanford formation constitutes most of the vadose zone. The suprabasalt sedimentary sequence at the Hanford Site is up to approximately 230-m (750-ft) thick in the west central Cold Creek syncline, while it pinches out against the Saddle Mountains anticline, Gable

S9211085.17

Figure 2.11. Generalized Stratigraphy of the Suprabasalt Sediments Beneath the Hanford Site

Mountain/Umtanum Ridge anticline, Yakima Ridge anticline, and Rattlesnake Hills anticline. The suprabasalt sediments are dominated by laterally extensive deposits assigned to the late Miocene- to Pliocene-aged Ringold formation and the Pleistocene-aged Hanford formation. Locally occurring strata assigned to the informally defined Plio-Pleistocene unit, early "Palouse" soil, and pre-Missoula gravels compose the remainder of the sequence. The geology of the Ringold and Hanford formations sediments is described in some detail because these sediments are the basis for determining vadose zone hydraulic properties for contaminant transport modeling.

2.1.6.2 Ringold Formation

The Ringold formation at the Hanford Site is up to 185-m (600-ft) thick in the deepest part of the Cold Creek syncline south of the 200 West Area and 170-m (560-ft) thick in the western Wahluke syncline near the 100 B Area. The Ringold formation pinches out against the Gable Mountain, Yakima Ridge, Saddle Mountains, and Rattlesnake Mountain anticlines. It is mostly absent in the northern and northeastern parts of the 200 East Area and adjacent areas to the north in the vicinity of West Pond.

The Ringold formation consists of semi-indurated clay, silt, compacted mud, fine- to coarse-grained sand, and granular to cobble gravel that usually are divided into the 1) gravel, sand, and paleosols of the basal unit; 2) clay and silt of the lower unit; 3) gravel of the middle unit; 4) mud and lesser sand of the upper unit; and 5) basaltic detritus in localized areas (Newcomb 1958; Newcomb et al. 1972; Myers et al. 1979; Bjornstad 1984; U.S. DOE 1988c). Ringold strata also have been divided on the basis of facies types (Tallman et al. 1981) and fining upwards sequences (PSPL 1982). Recent studies of the Ringold formation (Lindsey and Gaylord 1989; Lindsey 1991) indicate that the formation is best described and divided on the basis of sediment facies (individual stratigraphic bodies) associations and their distribution. Facies associations in the Ringold formation (defined on the basis of lithology, petrology, and stratification) include fluvial gravel, fluvial sand, overbank deposits, lacustrine deposits, and basaltic gravel. The Ringold formation is assigned a late Miocene to Pliocene age (Fecht et al. 1987; U.S. DOE 1988c). In general, the Ringold formation tends to be finer grained, or siltier in the upper parts that are just below the Hanford formation.

2.1.6.3 Hanford Formation

The Hanford formation consists of pebble-to-boulder gravel, fine- to coarse-grained sand, and silt. It can be divided into two main facies: coarse-grained or gravelly deposits and fine-grained or sandy and silty deposits. The Hanford formation also is commonly divided into two informal members: the Pasco gravels and the Touchet Beds (Myers et al. 1979; Tallman et al. 1981; et al. 1987; U.S. DOE 1988c). The Pasco gravels correspond to the gravelly facies, and the Touchet beds to the sandy to silty facies. The Hanford formation is thickest in the Cold Creek bar in the vicinity of the 200 West and 200 East Areas where it is up to 65-m (210-ft) thick. The Hanford Site deposits are absent on ridges above approximately 360 m (1,180 ft) above sea level.

The gravelly facies consists of coarse-grained sand and granule-to-boulder gravel that display massive bedding, plane to low-angle bedding, and large-scale cross-bedding in outcrop. Matrix commonly is lacking in gravels, giving them an open framework appearance. The gravelly facies dominates the Hanford formation in the 100 Areas north of Gable Mountain, the northern part of the 200 East Area, and the eastern part of the Site, including the 300 Area. In the 200 East and 200 West Areas, the facies association generally fines to the south, containing less gravel. The gravelly facies was deposited by high-energy flood waters in flood bars and along channelways such as the Ringold Coulee and Gable Mountain channel.

The sand and silt facies consists of silt and fine- to coarse-grained sand that commonly display normally graded rhythmites a few centimeters to several tens of centimeters thick in outcrop (Myers et al. 1979; U.S. DOE 1988c). This facies is found throughout the central, southern, and western Cold Creek syncline within and south of the 200 East and West Areas. These sediments were deposited under slack-water conditions and in backflooded areas (U.S. DOE 1988c).

2.1.6.4 Surficial Deposits

Holocene surficial deposits consist of silt, sand, and gravel that form a thin (<16 ft) veneer across much of the Hanford Site. These sediments were deposited by a mix of eolian and alluvial processes.

2.1.6.5 Geology of the Grout Treatment Facility

The geologic data used to determine the lithologic character of the vadose zone sediments and other suprabasalt sediments in the vicinity of the Grout Treatment Facility were derived largely from numerous wells both within and adjacent to the site. The location of these wells is shown in Figure 2.12 along with boundary locations of the 200 East Area and the Grout Treatment Facility, and the 216-B-3 Pond system (B Pond). Figure 2.12 also shows the locations of geologic cross sections, A-A' and B-B' through the grout disposal area.

Cross sections A-A' and B-B' derived from well logs from wells in and adjacent to the Grout Disposal Facility (Figures 2.13 and 2.14, respectively) depict the vertical and lateral variations in lithologic characteristics of both the Hanford and Ringold formations within and adjacent to the Grout Disposal Facility. They also show the location of the current water table, and the location of the 1944 water table, which is expected to be re-established after the B Pond system is no longer used. Samples from a characterization well (2-E25-234) that penetrated the upper part of the Hanford formation in the Grout Disposal Facility (Figure 2.13) and data from samples of other wells in the area were used to obtain saturated hydraulic conductivities and moisture retention characteristics of vadose zone sediments used in flow and transport modeling.

2.1.6.6 Geology Summary

The cross sections indicate that the sediments in the Grout Disposal Facility area exhibit considerable vertical and lateral variation in type and texture, but enough continuity is present to separate the

Figure 2.12. Location Map for the Grout Treatment Facility

September 1994

Hanford formation into an upper and lower unit based on a recognizable sandy gravel lithology characteristic of the lower unit. This separation also is consistent with regional 200 Area stratigraphy. Consequently, in developing the conceptual model (refer to Chapter 3.0), the Hanford formation is considered as two units. The north-south cross section, A-A', indicates that the Ringold formation becomes thinner from south to north. In the vicinity of the Grout Disposal Facility (below well 2-E25-234), the top of the Ringold formation is a silty sand compared with a more gravelly Hanford formation above. The water table for the unconfined aquifer is expected to be located in this upper Ringold formation unit after the B ponds are not used. Thus, the conceptual model will assume the vadose zone includes the entire Hanford formation plus a small part of the Ringold formation above the water table. For more details on the Grout Disposal Facility geology, see Lindberg et al. (1993), Appendix C.

2.1.7 Hydrology

This section describes the surface and subsurface hydrology of the Hanford Site region and the Grout Disposal Facility and also addresses an estimate of an appropriate recharge rate that will be adopted for modeling. A knowledge of the surface hydrology provides a basis for determining possible surface pathways for dissolved or suspended contaminants as well as identifying sources of infiltration. The groundwater hydrology helps determine possible flow paths for contaminants leached from the disposal facility, and provides a basis for determining vadose zone thickness. The regional surface and subsurface hydrology is discussed first, followed by hydrologic characteristics of the Grout Disposal Facility.

2.1.7.1 Surface Hydrology

Surface drainage enters the Pasco Basin from several other basins, including the Yakima River Basin, Horse Heaven Basin, Walla Walla River Basin, Palouse/Snake Basin, and Big Bend Basin (Figure 2.15). Within the Pasco Basin, the Columbia River is joined by major tributaries, including the Yakima, Snake, and Walla Walla rivers. No perennial streams originate within the Pasco Basin. Columbia River inflow to the Pasco Basin is recorded at the United States Geological Survey (USGS) gage below Priest Rapids Dam, and outflow is recorded below McNary Dam. Average annual flow at these recording stations is approximately $1.1 \times 10^{11} \text{ m}^3$ (8.7×10^7 acre-ft) at the USGS gage and $1.6 \times 10^{11} \text{ m}^3$ (1.3×10^8 acre-ft) at the McNary Dam gage (U.S. DOE 1988c). Total estimated precipitation over the basin averages 16.0 cm/yr (6.2 in./yr) as indicated in Section 2.1.5. Mean annual runoff from the basin is estimated to be less than $3.1 \times 10^7 \text{ m}^3/\text{yr}$ (2.5×10^4 acre-ft/yr), or approximately 3% of the total precipitation.

Primary surface-water features associated with the Hanford Site are the Columbia River and its major tributaries, the Yakima, Snake, and Walla Walla rivers. West Lake, located about 2.8 km (1.7 mi) north of the 200 East Area, is a shallow pond with an average depth of about 1 m (3 ft) and a surface area of about 40 hectares (10 acres). While described as a natural lake, the source of recharge to the lake is groundwater that is locally mounded because of infiltration from 200 Area operations. The pond represents a topographic depression that intersects the artificially elevated water table (U.S. DOE-RL 1993a; p. 3-10). When 200 Area disposal activities are halted, the water table will drop and West Lake will

Figure 2.15. Hydrologic Basins Designated for the Washington State Portion of the Columbia Plateau (U.S. DOE 1988c)

become an intermittent seasonal pond (U.S. DOE-RL 1993b). Wastewater ponds, cribs, and ditches associated with nuclear fuel processing and waste disposal activities also are present on the Site (Figure 2.16).

Routine water-quality monitoring of the Columbia River is conducted by DOE for both radiological and nonradiological parameters and has been reported by PNL since 1973. Washington State Department of Ecology has issued a Class A (excellent) quality designation for Columbia River water along the Hanford Reach from Grand Coulee Dam, through the Pasco Basin, to McNary Dam. This designation requires that all industrial uses of this water be compatible with other uses, including drinking, wildlife habitat, and recreation. In general, the Columbia River water is characterized by a low suspended load, a low nutrient content, and an absence of microbial contaminants (Woodruff et al. 1992).

Figure 2.16. Location of Water Disposal Ponds on the Hanford Site

The surface drainage characteristics of the Hanford Site and regional area indicate the Columbia River and its tributaries are the major surface drainage pathways, with the Columbia as the dominant pathway. The large volume of flow in the Columbia River through the Pasco Basin and downstream permits considerable dilution. No surface streams are near the Grout Disposal Facility, but current disposal ponds have an artificial influence on net contributions to the water table. These disposal ponds and related facilities are not expected to exist after current operations are terminated, so their long-term influence is not considered in this performance assessment.

2.1.7.2 Subsurface Hydrology

The groundwater pathway is considered the most likely pathway for contaminants released from the vault because of the low precipitation in the Pasco Basin, the lack of surface transport pathways near the Grout Disposal Facility, and the subsurface location of the vaults. To evaluate this pathway, information is required about the types of aquifers present, depths to the water table, regional flow paths, and the net recharge rate. This section summarizes the regional hydrogeology of the Hanford Site and the more localized hydrology of the Grout Disposal Facility. More details on the hydrology of the Grout Disposal Facility are presented in Lindberg et al. (1993) (Appendix C). A summary of studies related to evaluating the net recharge rate also is given in this section.

The hydrogeology of the Pasco Basin is characterized by a multiaquifer system that consists of four hydrogeologic units corresponding to the upper three formations of the Columbia River Basalt Group (Grande Ronde Basalt, Wanapum Basalt, and Saddle Mountains Basalt) and the suprabasalt sediments. The basalt aquifers consist of the tholeiitic flood basalts of the Columbia River Basalt Group and relatively minor amounts of intercalated sediments of the Ellensburg formation. Confined zones in the basalt aquifers are present in the sedimentary interbeds and/or interflow zones that occur between dense basalt flows. The main water-bearing portions of the interflow zones are networks of interconnecting vesicles and fractures of the flow tops and flow bottoms (U.S. DOE 1988c). The suprabasalt sediment or uppermost aquifer system consists of fluvial, lacustrine, and glaciofluvial sediments. This aquifer is regionally unconfined and is contained primarily within the Ringold formation and Hanford formation. This unconfined aquifer is considered the primary pathway for use in modeling possible contaminant transport from the Grout Disposal Facility. The conceptual model of the unconfined aquifer is discussed in Chapter 3.0 and modeling results are given in Chapter 4.0.

The uppermost aquifer system is regionally unconfined beneath the Hanford Site and lies at depths ranging from less than 0.3 m (1 ft) below ground surface near West Lake and the Columbia and Yakima rivers, to greater than 106.7 m (350 ft) in the central portion of the Cold Creek syncline. Groundwater in this aquifer system occurs within the glaciofluvial sands and gravels of the Hanford formation and the fluvial/lacustrine sediments of the Ringold formation. The position of the water table in the southwestern Pasco Basin is generally within Ringold fluvial gravels. In the northern and eastern Pasco Basin the water table is generally within the Hanford formation. The main body of the unconfined aquifer generally occurs within the Ringold formation. The base of the uppermost aquifer system is defined as the top of the uppermost basalt flow. Hydraulic conductivities of the Hanford formation are generally greater than

for the gravel facies of the Ringold formation (Graham et al. 1981). However, fine-grained deposits in the Ringold formation locally form confining layers for Ringold fluvial gravels. The uppermost aquifer system is bounded laterally by anticlinal basalt ridges and is approximately 152.4-m (500-ft) thick near the center of the Pasco Basin.

Before the liquid waste disposal systems such as B Pond began operating, and before the onset of large regional irrigation projects, the groundwater table for the Hanford Site can be represented by a 1944 water table map (Figure 2.17). The 1944 water table contours suggest that groundwater flow is easterly toward the Columbia River and the hydraulic gradient is relatively uniform in the midsection of the Hanford Site. Before operations at the Hanford Site began in 1944, the hydraulic gradient in all but the

Figure 2.17. Hindcast Water Table Map of the Hanford Site, January 1944 (ERDA 1975)

southwestern-most portion of the Hanford Site was approximately 1.5 m/km (5 ft/mi). Regional groundwater flow was generally toward the east-northeast, although flow north of Gable Mountain was more to the north. Artificial recharge of the uppermost aquifer system currently occurs from the disposal of large volumes of wastewater on the Hanford Site (principally the 200 Areas) with minor influence from regional irrigation projects. Effluent disposal at the Hanford Site has altered hydraulic gradients and flow directions, particularly in the vicinity of the 200 Areas and the Grout Disposal Facility. Figure 2.18 shows the current water table map influenced by effluent disposal actions. Groundwater flow is still nominally easterly toward the Columbia River, but there is evidence of mounding in the 200 East Area near B Pond. Groundwater flow north of Gable Mountain now trends in a more northeasterly direction as a result of mounding near reactors and flow through Gable Gap (the gap between Gable Mountain and Gable Butte). South of Gable Mountain, flow is interrupted locally by the groundwater mounds in the 200 Areas. A component of groundwater flow is to the north between Gable Mountain and Gable Butte from the 200 Areas. Relative to the time periods considered in this performance assessment, effluent disposal operations will have ceased to function. Thus, modeling activities used for this performance assessment assume a water table consistent with the 1944 map (see Figure 2.17).

2.1.7.3 Subsurface Hydrology of the Grout Treatment Facility

As discussed above in terms of regional groundwater flow, groundwater flow beneath the 200 East Area is complex because of the convergence of flow from the west (local groundwater flow system) and east (B Pond artificial recharge). This convergence of flow has caused groundwater within the unconfined aquifer to depart from historical flow paths, with a component flowing northward between Gable Butte and Gable Mountain and another component flowing southeast toward the Columbia River (see Figure 2.18). In addition, the high transmissivity beneath most of the 200 East Area (due to the presence of the current water table in the gravel-rich part of the lower Hanford formation) results in low hydraulic gradients. Groundwater flow direction has changed temporarily because of changing rates of wastewater discharged to B Pond and other disposal sites. Therefore, it is often difficult to define groundwater flow direction from water table maps of the 200 East Area. However, contaminant plume maps indicate long-term trends in groundwater flow directions (Serkowski and Jordan 1989). These plume maps indicate a north-northwest direction of flow in the extreme north central portion of the 200 East Area and a south to southeast direction of flow in the southeast portion of the 200 East Area. Details of a recent water table map in the 200 Areas, along with the distribution of a number of wells, including monitoring wells, are shown in Figure 2.19.

The uppermost aquifer system (unconfined aquifer) within and adjacent to the Grout Treatment Facility is defined as the saturated units above the uppermost basalt. The permeable portion of the uppermost aquifer system consists of the lower gravel of the Hanford formation and Ringold units A and E (fluvial gravel). Where present, the lower mud of the Ringold formation acts as a confining layer to Ringold unit A. The base of the uppermost aquifer system is the Elephant Mountain Member of the Saddle Mountain Basalt formation. An isopach (thickness) map of the unconfined aquifer is shown in

Figure 2.18. Hanford Site Water Table Map, June 1989 (Smith and Gorst 1990)

Figure 2.20. The uppermost aquifer system thickens to the south within the map area. The map was constructed by taking the difference in elevation between the water table and the top of the basalt. As indicated, the aquifer is about 20-m thick in the north area and 50-m thick in the south area.

The top of the uppermost aquifer system within the study area is contained within either Ringold fluvial gravel unit A, or E, the Hanford formation lower gravel sequence (or undifferentiated Hanford

Figure 2.19. 200 Areas Water Table Map, June 1990 (Kasza, Harris, and Hartman 1990)

Figure 2.20. Isopach Map of the Uppermost Aquifer System Indicating Thickness of the Unconfined Aquifer

formation gravel), or the Hanford sandy sequence. Figure 2.21 shows the geologic units that the water table intersects. Within the western portion of the Grout Treatment Facility, the water table is contained within the Ringold fluvial gravel unit A. The water table occurs within the Hanford formation lower gravel sequence in the eastern portion of the map area. In the western portion of the map area, the water table occurs within the Ringold gravel units A and E and the Hanford formation sandy sequence. After operation of the disposal ponds is discontinued, the unconfined aquifer will be thinner and the water table is expected to be contained in the Ringold formation in the vicinity of the Grout Disposal Facility.

Hydraulic properties of transmissivity and/or hydraulic conductivity have been determined from some of the wells in the map area and are reported in Appendix C. Comparisons of equivalent hydraulic conductivities determined from pumping tests (i.e., Graham et al. 1981 and Appendix C) and the values

- Hanford Gravels*
- Hanford Sand Sequence
- Ringold Gravel Unit E
- Ringold Lower Mud Unit
- Ringold Gravel Unit A

- Facilities**
- B Pond
- Grout Treatment Facility

* This includes upper, lower, and undifferentiated Hanford Gravels

S9211085.20

Figure 2.21. Geologic Map of the Water Table Showing the Lithologic Units in the Vicinity of the Grout Disposal Facility that Intersect the Water Table

of saturated K given in Appendix J (Rockhold, Fayer and Heller 1993) indicate that values from pumping tests are greater by orders of magnitude. The values reported in Appendix J and used in this performance assessment for vertical hydraulic conductivity are from a small volume sample that was repacked in the laboratory. The pump test values (Appendix C) are for horizontal conductivity for a large volume of material influenced by pumping tests. The ratio of horizontal-to-vertical conductivity was previously reported to range between 16 and 13 for a well located northeast of the Grout Disposal Facility (Graham et al. 1981). This reported ratio does indicate the expected trend of horizontal conductivity exceeding vertical conductivity; however, it does not account for the differences in the values reported in Appendices C and J. Measurements reported in these appendices are not of the same materials. The Graham et al. (1981) report is an interpretation of anisotropy of a single point in the aquifer. The high saturated horizontal hydraulic conductivity reported in Appendix C suggests that once contamination is in the aquifer it could move rapidly to a well located 100-m downgradient, and its movement could be caused by a very low hydraulic gradient. The magnitude of the horizontal hydraulic conductivities also suggests that layers of well-sorted gravels may exist, and, therefore, capillary breaks could exist in the vadose zone. Such geohydrologic structures within the vadose zone can cause lateral migration of water and contaminants. Some direct evidence for this is available from maps of contaminant plumes accompanied by large liquid volumes from previous single-shell tank leaks at the Hanford Site (Routson et al. 1979). Because releases from grout vaults are not accompanied by large liquid releases, dispersion was neglected in modeling flow and transport through the vadose zone, and because vertical flow should dominate, the laboratory-measured saturated hydraulic conductivities were applied.

2.1.7.4 Natural Recharge Rates

Recharge is the net amount of total precipitation that infiltrates into the unsaturated zone after runoff, evaporation, and transpiration by plants have occurred. Recharge from rain and snowmelt sources is a major hydrologic variable required to evaluate contaminant transport from the Grout Disposal Facility. Studies conducted over the last 20 years at the Hanford Site indicate that recharge can be highly variable depending on factors such as climate, vegetation, and soil texture. These studies are summarized below.

Bauer and Vaccaro (1990) estimated groundwater recharge for the Hanford Site as part of their study of recharge affecting the Columbia Plateau regional aquifer. Using daily precipitation and temperature data for the period 1956 through 1977, and a water budget model, they estimated recharge for sub-areas of the Hanford Site ranging in size from 65 to 260 hectares (0.25 to 1.0 mi²). Their model included the following physical processes: snow accumulation and melt, interception of precipitation, surface runoff, evaporation from foliar cover, evaporation from bare soil, and plant transpiration. It accounts for the influences of soil type, land use, plant growth, altitude, slope, and aspect. The long-term (i.e., 21-year) average of annual recharge for the entire Hanford Site was estimated to be 0.97 cm/yr (0.38 in./yr). They estimated a long-term average recharge rate of 0.25 to 1.27 cm/yr (0.1 to 0.5 in./yr) at the location of the Grout Disposal Facility on the 200 Area plateau.

Routson and Johnson (1990) reviewed water infiltration data from a 13-year observation period of the closed-bottom lysimeter located in the 200 East Area, and cesium-137 profile data from a solid waste

burial ground trench in the 200 West Area. They concluded that for the natural soils and vegetation of the 200 Area plateau and for areas where natural near-surface conditions could be restored, the potential for downward movement of contaminants in the upper vadose zone is minimal. The recharge rate of the closed-bottom lysimeter was estimated to be 0.0 ± 0.2 cm/yr based on the 13-year record. They recommended that management and cleanup efforts strive to maintain or recreate natural soil and vegetative cover conditions.

Gee et al. (1992) reviewed all published recharge studies for the Hanford Site and described the reasons for highly variable observations of recharge. They describe the roles played by the three major factors of climate, soil, and vegetation. Clearly, recharge is directly related to annual precipitation; where recharge is observed, more precipitation implies more recharge. Also, recharge has been shown to depend on the seasonal distribution of precipitation, with maximum recharge events occurring after the wettest winter periods. Recharge is greatest for coarse-textured soils; least for fine-textured soils. It is greatest for surfaces that are maintained free of vegetation; least for surfaces supporting both shallow- and deep-rooted vegetation. Gee et al. (1992) discuss the variability of recharge at the Hanford Site and evaluate the results of a number of lysimeter studies. They conclude that under normal vegetated conditions in fine soils, recharge may be near zero.

The results of research reported by Gee et al. (1992) are more relevant to the surface barrier because the surface barrier involves silt loam soils, vegetation, and climate specific to the barrier design and 200 Area plateau. The finding that occasional range fires have only a short-term impact on the vegetation further supports neglecting short-term ecological variability in assessing long-term performance. Thus, the interpretation of field observations and supporting simulations of the near-surface environment, that there will be negligible or nonmeasurable recharge through an isolation barrier (see Section 2.7), is adopted. The net infiltration design goal for the permanent isolation barrier is 0.05 cm/yr (i.e., a non-zero value), because the field measurement program could not achieve an absolute zero recharge goal. This value could have been adopted as the infiltration rate for the performance assessment analyses; however, it was doubled and the value 0.1 cm/yr was adopted to provide additional conservatism.

2.1.8 Regional Background Contamination and Site Monitoring

Wastewaters discharged on the Hanford Site have reached the unconfined aquifer and the confined aquifer of the Rattlesnake Ridge interbed. The primary constituents that have reached the upper confined aquifer and the uppermost aquifer system are tritium, iodine-129, ruthenium-106, technetium-99, uranium, nitrate, and chromium (U.S. DOE 1986a). The groundwater is monitored routinely and extensively to record the movement of contaminants and to determine any impact from the Site to the public. Groundwater monitoring reports are produced annually (e.g., Swanson et al., 1988, Serkowski and Jordan 1989, and Woodruff et al. 1992). Annual reports based on monitoring wells adjacent to the Grout Disposal Facility are sampled quarterly as part of RCRA requirements (Swanson et al. 1988). These sample results can vary depending on local operations, so a regional baseline study was conducted using these and other site-wide monitoring results (Johnson 1993). Background levels from this study are given in Table 2.1 (Johnson 1993), along with tentative threshold levels.

Table 2.1. Provisional Background Values for Hanford Site Groundwater^(a)

Constituent (Conc.)	PNL Results ^(b)	WHC Provisional Threshold Values
Aluminum (ppb)	<2	<200
Ammonium (ppb)	<50	<120
Arsenic (ppb)	3.9±2.4	10
Barium (ppb)	42±20	68.5
Beryllium (ppb)	<0.3	<5
Bismuth (ppb)	<0.02	<5
Boron (ppb)	<50	<100
Cadmium (ppb)	<0.2	<10
Calcium (ppb)	40,400±10,300	63,600
Chloride-All (ppb)	10,300±6,500	NC
Chromium (ppb)	4±2	<30
Copper (ppb)	<1	<30
Fluoride (ppb)	370±100	1,340 775 ^(c)
Iron-Mid (ppb)	NA	291
Lead (ppb)	<0.5	<5
Magnesium (ppb)	11,800±3,400	16,480
Manganese-All (ppb)	7±5	NC
Mercury (ppb)	<0.1	<0.1
Nickel (ppb)	<4	<30
Nitrate (ppb)	NA	12,400
Phosphate (ppb)	<1,000	<1,000
Potassium (ppb)	4,950±1,240	7,975
Selenium (ppb)	<2	<5
Silver (ppb)	<10	<10
Silicon (ppb)	NA	26,500
Sodium (ppb)	18,260±10,150	33,500
Strontium (ppb)	236±102	264.1
Sulfate (ppb)	34,300±16,900	90,500
Uranium (pCi/L)	1.7±0.8	3.43
Vanadium (ppb)	17±9	15
Zinc-All (ppb)	6±2	NC
Field Alk. (ppb)	NA	215,000
Lab Alk. (ppb)	123,000±21,000	210,000
Field pH	NA	(6.90, 8.24)
Lab pH	7.64±0.16	(7.25, 8.25)
TOC (ppb)	586±347	2,610 1,610 ^(c)
Field Cond. (umho/cm)	NA	539
Lab Cond. (umho/cm)	380±82	530

Table 2.1. (contd)

Constituent (Conc.)	PNL Results ^(b)	WHC Provisional Threshold Values
TOX, LDL (ppb)	NA	60.8 37.6 ^(c)
Total Carbon (ppb)	NA	50,100
Gross Alpha (pCi/L)	2.5±1.4	63 5.79 ^(c)
Gross Beta (pCi/L)	19±12	35.5 12.62 ^(c)
Radium (pCi/L)	<0.2	0.23

(a) From Tables 5-9 and 5-11 of DOE/RL-92-03 (U.S. DOE-RL 1992a).

(b) Results shown are mean ± one standard deviation.

(c) Potential outlier observation(s) were removed.

NA = not available; NC = not calculated.

2.1.8.1 Radiological Background

Various natural and human-produced sources of radiation, including natural terrestrial and cosmic background radiation, medical treatment and x-rays, natural internal body radioactivity, and inhalation of naturally occurring radon, contribute to radiation doses. The national average for these doses is provided in Figure 2.22. Of the contributions shown in Figure 2.22, natural background contributes 300 mrem to the estimated per capita dose to individuals living near the Hanford Site. Human-produced sources contribute an additional 65 mrem/yr. In contrast, annual Hanford Site environmental reports such as Woodruff et al. (1992) estimate that the maximum dose to an individual from Hanford Site operations in 1991 was about 0.02 mrem. A summary of doses to the public in the vicinity of the Hanford Site from various sources in 1991 is given in Table 2.2 (Woodruff et al. 1992).

Other non-DOE industrial sources of public radiation exposure exist at or near the Hanford Site. These include the low-level radioactive waste burial site at Hanford operated by U.S. Ecology, the nuclear generating station at Hanford operated by the Washington Public Power Supply System, the nuclear fuel production plant operated by Siemens Nuclear Power Corporation, the low-level waste compacting facility operated by Allied Technology Corporation, and a decontamination facility operated by Pacific Nuclear Services. Based on information gathered from these companies, Woodruff et al. (1991) determined that the total 1990 individual dose from those activities was approximately the same as that from DOE operations at the Hanford Site (0.03 mrem). The 1991 estimate is 0.02 mrem (Woodruff et al. 1992), as indicated above.

S9203058.94

Figure 2.22. Averages for Natural and Human-Produced Sources of Radiation (NCRP 1987)

Table 2.2. Dose Summary from Hanford Site Operations
(Woodruff et al. 1992)

	Total Hanford Effluents ^(a)	Hanford Airborne Effluents
Maximum Individual Dose, mrem/yr	0.02	0.007
DOE Limit or EPA Standard	100.0	10.0
Percent of Limit or Standard	0.02	0.07
Percent of Natural Background Radiation	0.007	0.002

(a) Includes all air and water effluents beyond site boundary. Dose estimate based on hypothetical maximum individual.

(b) Background estimated to be 300 mrem/yr.

2.1.9 Seismic Activity

This section describes the seismic history of the Hanford Site and summarizes the earthquake potential that the Grout Treatment Facility might experience. This history provides a basis for subjective estimates of future seismic activity. For long-term evaluation of the Grout Disposal Facility, it is assumed that earthquake loads will have a cumulative effect over time.

Eastern Washington and, in particular, the Columbia Plateau region is a seismically inactive area when compared to the rest of the western United States (U.S. DOE 1988c). The closest regions of historic moderate-to-large earthquake generation are in western Washington and Oregon, western Montana, and eastern Idaho. The most significant event relative to the Hanford Site is the 1936 Milton-Freewater, Oregon earthquake that had a magnitude of 5.75 on the Richter scale and occurred more than 90 km (54 mi) away. The largest Modified Mercalli Intensity was felt at Walla Walla, Washington and was VII. This event was approximately 105 km (63 mi) from the Hanford Site.

Westinghouse Hanford operates a 20-station seismic network in and around the Hanford Site that is capable of locating all earthquakes of Richter magnitude 1.5 and larger at or near the Hanford Site, and magnitude 2.0 and larger throughout the rest of southeastern Washington. The historic seismic record for eastern Washington began in approximately 1850, and no earthquakes large enough to be felt had epicenters on the Hanford Site. The only evidence of past moderate or possibly large earthquake activity is geologic evidence. This evidence is shown by the anticlinal folds and faulting associated with Rattlesnake Mountain, Saddle Mountain, and Gable Mountain. The presently recorded seismic activity related to these structures consists of micro-size earthquakes. The suggested recurrence rates of moderate and larger size earthquakes on and near the Hanford Site are measured in geologic time (tens of thousands of years).

2.1.9.1 Long-Term Structural Evaluation Performance Criteria

This discussion addresses the earthquake loads that the Grout Disposal Facility is likely to experience during the performance period. Predicted frequencies of seismic events as a function of peak ground acceleration are shown in Figure 2.23. Earthquake loads are presented for the long-term structural performance assessment.

The freestanding grout disposal vaults and the waste feed system are designed to withstand an earthquake of 0.25-G horizontal and 0.17-G vertical acceleration (U.S. DOE 1990b, Section 2.4.2). A 0.25-G ground motion has a return period of about 10,000 years (probability of exceeding 10^{-4}) (WCC 1989). As shown in Table 2.3, the probability of exceeding a 0.25 G ground motion in 1,000 years is only 10%.

Those elements of the Grout Disposal Facility that serve as barriers in the overall performance assessment must continue to perform at some level throughout the performance period. The deterioration of the barrier will occur over the long-term performance period (e.g., 500, 1,000, 10,000 years). This

Figure 2.23. Comparison of Seismic Hazard for Various Regions of the Hanford Site

performance assessment considers both physical and chemical degradation of the barrier(s). Deformation and/or cracking from earthquake ground motion is one form of physical degradation.

The asphalt barrier performance could be assessed for 0.25 G and 0.35 G. Further, 0.25 G is the seismic design basis for DOE's FFTF and the Supply System, Unit 2 commercial power reactor, both of which are on the Hanford Site and were reviewed by the U.S. Nuclear Regulatory Commission (NRC)

Table 2.3. Approximate Probability of Exceedance During Selected Time Periods for Three Ground Motions

Ground Motion (G)	Return Period Years	Annual Prob. of Exceed. (p)	(EP) in 50 Years ^(a)	(EP) in 150 Years	(EP) in 500 Years	(EP) in 1,000 Years	(EP) in 10,000 Years
	1,000 ^(b)	$10^{-3(b)}$	5% ^(b)				
0.12	2,500	4×10^{-4}	2%	6% ^(b)	10%	33%	90%
0.25	10,000	10^{-4}	0.5%	1.5%	5% ^(b)	10%	63%
0.35	18,000	5.6×10^{-5}	0.3%	0.1%	3%	5% ^(b)	43%

(a) $EP = 1 - (1 - p)^n$

where p = the annual probability of exceedance,

n = the design/performance life, and

EP = the probability of exceedance over the design/performance life.

(b) Entries represent DOE guidance for a moderate hazard facility.

(U.S. NRC 1978, 1982). The NRC seismic assessment guidance for a low-level radioactive waste disposal facility (10 CFR 61) is essentially the same as that for a nuclear power reactor (10 CFR 100), as both require the application of 10 CFR 100, Appendix A. Therefore, 0.25 G is comparable to the NRC seismic design criteria requirement for an NRC-licensed, commercial low-level radioactive waste disposal facility having a performance life of 500 years. Structural analysis and performance assessment to 0.35 G would provide additional confidence and data for the performance assessment in performance periods longer than those required by the NRC (i.e., greater than 500 years).

The probability of exceeding the ground motions during several time periods is illustrated in Table 2.3. The DOE guidance for a moderate hazard facility is shown in the first line of the table. The table shows that the probability of exceeding 0.25 G in 500 years and 0.35 G in 1,000 years is about 5%, or comparable to the DOE's guidance for a moderate hazard facility. Extension of the performance period results in higher probability of exceeding a ground motion. This is illustrated for a 10,000-year performance period and can be calculated for any length of time as needed.

2.2 Waste Characteristics and Inventory

This section summarizes the general characteristics of waste that will become the waste feed stock for the Grout Treatment Facility, the various sources of this waste, estimates of the total volume of waste to be processed, and the average composition of the waste. The estimates of total waste volume and average composition are based on three types of information. These include 1) analytical data of samples taken from tanks, 2) estimates or analyses from process streams from the 242-A Evaporator/Crystallizer and waste transfer history, and 3) estimates from pretreatment flow sheets that describe the expected

low-level waste streams that will be generated from pretreatment processes for various high-level and transuranic (TRU) wastes. The uncertainty with each of these three approaches for estimating inventory increases respectively from direct sampling/analysis, to process and transfer history, to pretreatment estimates. In practice, the 33-vault Grout Disposal Facility will consist of groups of vaults with grouts made with several different waste streams. Each group requires modified formulations, but specific waste streams and formulations for the entire Grout Disposal Facility are not yet defined. Consequently, an average waste composition for the total volume of waste that is expected to be disposed of is used to determine dose estimates for this performance assessment. This section summarizes the methodology used to determine the waste inventory and includes a summary of waste inventory. A detailed description of waste characteristics, including detailed composition tables and uncertainty in standard deviations and waste sources and calculational methodology, is provided by Hendrickson and Conner (1993) (see Appendix E).^(a)

The use of the average expected waste composition for this analysis differs from the approach used in regulatory safety analyses, for which a bounding (worst case) inventory was used. The use of different approaches is justified by the different philosophy and purpose of the documents. The performance assessment is written to provide an estimate of the long-term impacts of the disposal action. The regulatory safety documentation is written to provide an upper bound for acute releases and impacts from postulated accidents during operation of the facility.

2.2.1 Waste Description

The waste to be disposed at the Grout Disposal Facility is a concentrated salt solution produced by facility operations, laboratories, and decontamination activities in the 100, 200, 300, and 400 Areas of the Hanford Site. The waste from the operating units is transferred to the double-shell tank system for interim storage. Some of the waste is concentrated using evaporation to minimize its volume. This performance assessment refers to the potential candidates for grout disposal as double-shell tank waste and to double-shell tank waste pretreated or adjusted for heat limitations as grout waste feed.

The overall composition for this waste is estimated based on sampling, the historic record of processing, and future plans for processing of the waste. Waste processing, other than the disposal action described in this performance assessment, includes waste evaporation, decanting, radioactive isotope scavenging (e.g., cesium-137 for capsules), and pretreatment operations such as cesium ion exchange and TRUEX.

(a) A minor change to some of the estimated radionuclide concentrations was recently made (Hendrickson 1993; Engineering Change Notice 163849) but is not expected to significantly impact dose calculations. The inventory data in Appendix E was used in this performance assessment. An updated copy of Appendix E that incorporates the minor change now appears in Appendix R.

The following general observations regarding radionuclides, chemicals, and organics in the expected waste can be made. Additional details regarding waste composition are provided in Appendix E.

- **Radionuclides** - In terms of activity, the major radionuclides present in the waste are cesium-137 and strontium-90. Although the isotopic species distribution is broad, 96% of the overall parent activity of 0.15 Ci/L is ascribed to cesium-137 (87.3%) and strontium-90 (8.5%). The major radionuclides of apparent concern for groundwater pathway analyses are iodine-129 ($8 \times 10^{-5}\%$ of mean activity), technetium-99 ($3 \times 10^{-2}\%$ of mean activity), and neptunium-237 ($3 \times 10^{-4}\%$ of mean activity).
- **Chemicals** - the predominant inorganic cations are aluminum (0.45 M), potassium (0.2 M), fluoride (0.7 M), and sodium (5.5 M). The predominant inorganic anions are nitrate (2.7 M), hydroxide (1.1 M), and nitrite (0.5 M). The solution pH is typically about 12. The waste material has a high total dissolved and suspended solids mean level of approximately 420 g/L and a mean density of 1,300 g/L.
- **Organics** - the total organic carbon (TOC) content has a mean value of approximately 4.3 g/L, which is not sufficient to support combustion. The primary organic constituents in the waste liquid are the alkaline forms of citric acid, N-hydroxyethylenediaminetriacetic acid (HEDTA), hydroxyacetic acid, ethanedioic acid, and ethylenediamine tetra-acetic acid (EDTA). Each of these is an organic acid, with their mean total comprising approximately 92% by weight of the total organic constituents expected.

2.2.2 Waste Sources and Volumes

Three sources of wastes and the associated processing requirements before grouting the wastes are schematically illustrated in Figure 2.24. These three sources are 1) the concentrated wastes that must be blended with dilute wastes before forming the grout slurry, 2) the wastes generated by the evaporator/crystallizer with a low-level fraction that can be sent directly to the Grout Disposal Facility, and 3) the various high-level and TRU wastes currently in tanks that will be pretreated to generate a low-level fraction. The low-level fraction will be sent to the Grout Processing Facility, while the high-level and transuranic (TRU) fraction is vitrified. The components that currently exist, such as concentrated wastes in tanks, the evaporator, the Grout Processing Facility, and four vaults, are shown in Figure 2.24 as black symbols. Open symbols depict components that do not currently exist; these include the pretreatment facility, pretreated low-level waste tanks, and future grout vaults. The number of open symbols relative to black symbols is proportional to future waste volumes.

The total volume of wastes to be processed is estimated to be 122 million liters (32.2×10^6 gal). This volume of materials, described further in the following paragraphs, includes existing concentrated

S9211085.9

Figure 2.24. Grout Waste Feed Sources and Volumes (10^6 Gallon Increments)
(Does not show existing vault filled with PSW grout.)

wastes, future concentrated wastes, and the low-level streams from the treatment of neutralized current acid waste (NCAW), neutralized cladding removal waste (NCRW), Plutonium Finishing Plant (PFP) waste, and complexed concentrate (CC) waste.

The Hanford Site facilities waste (HFW) includes the wastes generated on the Hanford Site at locations other than the 200 Area operations. The N Reactor, located in the 100 N Area, produced three liquid waste streams. One stream, the N Reactor decontamination waste stream, is generated periodically during cleanup operations. Ion-exchange regeneration waste is produced semicontinuously when back-flushing the ion exchange resins used to purify the water in the spent-fuel storage basin. The combined waste streams from decontamination activities ion exchange regeneration are also known as phosphate/sulfate waste (PSW).

A third waste stream, the sandfilter backwash waste, was primarily a sludge generated during periodic filter flushing. Other HFW secondary waste streams result from fuel fabrication operations and laboratory activities from the 300 Area, and miscellaneous wastes from the 400 Area.

Many streams that enter double-shell tanks consist of dilute liquids low in radioactivity. These streams are so concentrated by Evaporator 242-A such that one additional pass through the evaporator would increase the sodium aluminate concentration beyond the sodium phase boundary and the stream would solidify when cooled. Just before reaching this phase boundary, the waste stream from the evaporator is called double-shell slurry feed (DSSF).

When the DSSF is processed through Evaporator 242-A, it is concentrated past the sodium aluminate phase boundary. The hot slurry is pumped to a double-shell tank where it forms solids as it cools. This waste is called double-shell slurry (DSS).

Concentrated phosphate waste is a blend from different waste sources. Approximately half is phosphate waste derived from N Reactor decontamination operations. The remainder is primarily derived from previous salt well pumping operations (liquids pumped from single-shell tanks). During retrieval, some liquids may be added to facilitate pumping of this waste.

Cladding removal waste (CRW) results from the dissolution of the N Reactor spent fuel Zircaloy cladding using the Zirflex process in the PUREX reprocessing plant. Neutralization of this waste causes most of the zirconium to precipitate as a hydrated oxide, essentially removing all of the actinides and fission products from the solution. However, sufficient fine plutonium particles are entrained with the precipitated zirconium that the waste collected in the double-shell tanks is considered to be a TRU waste. The waste sludge and supernatant as stored in the double-shell tanks is known as NCRW.

NCAW is the aqueous high-salt waste from the first-cycle solvent extraction column at the PUREX plant. NCAW contains TRU elements and fission products. The sludge will be separated from the NCAW for disposal. Transuranic-reduced supernatant liquid will be grouted for disposal.

The PFP aqueous waste originates from the conversion of plutonium nitrate to oxide or metal and includes TRU laboratory wastes. The PFP waste also includes Plutonium Reclamation Facility (PRF) waste consisting of high-salt solvent extraction waste and organic wash waste. Supernatant wastes from the PFP will be disposed in grout following separation of solids.

Complexant concentrate waste results from concentration of wastes containing large amounts of organic complexing agents. These organic compounds were introduced to the waste during strontium recovery processing in the B Plant.

The volume distribution of the wastes to be grouted is shown in Figure 2.25. Approximately 50% of the waste feed is to be composed of the low-level streams from pretreatment of high-level and TRU wastes. Approximately 25% DSSF is attributed to the evaporative product of future dilute wastes

S9211085.44

Figure 2.25. Waste Source Volume Distribution for Grout Disposal

resulting from facility operations and decontamination. Slightly less than 18% currently exist as concentrated wastes in Tanks 106-AN, 101-AW, 105-AP, 104-AN, 105-AN, and 103-AN. These wastes do not necessarily require pretreatment before disposal. The balance consists of dilute wastes that may be blended with the concentrated wastes to reduce the radiogenic thermal load on the vault structures.

2.2.3 Expected Waste Composition

A detailed analysis of all waste sources, volumes, and concentrations expected to be received by the Grout Treatment Facility is given in Hendrickson and Conner (1993) (Appendix E), along with a complete description of the methodology and assumptions used to calculate the total inventory of the waste that will be contained in all 33 grout vaults. In general, three approaches were taken to arrive at inventory estimates. For existing wastes that have been sampled and analyzed, the weighted averages of measured constituents in individual tanks plus correlation factors for those constituents that were not measured in all tanks were used to calculate concentrations. For evaporator-derived wastes, a volume reduction factor was used along with concentrations to determine contributions from this source. Also, appropriate operating records were used to determine transfer history that included waste volumes transferred and their concentrations. For low-level waste streams that will be generated by future pretreatment, the most current and complete material balances were used. Flowsheets that were developed based on current

knowledge of NCAW, NCRW, CC, and PFP wastes and the associated current pretreatment plans were used to derive low-level waste volumes and concentrations from this source. Specific details on the methodology used for these calculations are given in Hendrickson and Conner (1993) (see Appendix E). Specialized methods for estimating concentrations of some critical radionuclides, such as cesium-135 and americium-241 as well as TRU limitations, are also given in Appendix E. All radionuclide activities are shown as of October 1, 1993.

These three approaches were combined to yield an inventory concentration estimate to calculate doses for the various exposure scenarios. The complete inventory is a combination of data appearing in Tables 4 and 8 of Appendix E and is based on estimates of the following:

- compositions of dilute wastes
- concentrated wastes to be produced in the future
- currently available concentrated feed
- all expected materials subject to pretreatment.

Total feed concentrations for chemicals (in molarity, mol/L) and radionuclides (in $\mu\text{Ci/L}$) are summarized in Table 2.4. Molecular weight and decay half-life data used in the conversion of molarity (M) and in transport simulations are also provided. The bulk inventory of each chemical (in kg) and radionuclide (in Ci) constituent is also presented. Because the inventory was being updated while simulations were being conducted, there are some discrepancies between the inventory that appears in Appendix E and the inventory actually simulated. These discrepancies are noted in footnotes to Table 2.4. Minor differences in decay half-life and molecular weight data arising from the use of different data sources by inventory and geochemistry-transport groups are also noted in the table.

As additional tanks are sampled and analyzed and the waste being disposed of in grout is better defined, the level of uncertainty in the inventory value will decrease. The total inventory for each radionuclide in Table 2.4 is considered the maximum inventory that can be disposed of in grout under this performance assessment. If the inventory to be disposed exceeds the Table 2.4 values, the impact on the performance assessment analyses will be evaluated and the performance assessment revised as required.

Uncertainty in terms of overall standard deviations is discussed in Appendix E (Section 3.4.4), and analytical error with specific tank sampling programs is shown in specific tank analytical data included in Appendix E tables.

2.2.4 Waste Classification

Low-level waste is defined in DOE Order 5820.2A as "waste that contains radioactivity and is not classified as high-level waste, transuranic waste, or spent nuclear fuel or 11e(2) byproduct material as

Table 2.4. Waste Components Analyzed in This Performance Assessment

Waste Component: Chemicals	Total Feed: Concentration (M) ^(a)	Total Inventory: (kg) ^(b)	Molecular Weight (g/mol)
Ag	6.48×10^{-5}	8.53×10^2	107.868
Al	4.48×10^{-1}	1.47×10^6	26.9815
As	1.99×10^{-4}	1.82×10^3	74.9216
B	3.37×10^{-3}	4.44×10^3	10.81
Ba	8.22×10^{-5}	1.38×10^3	137.33
Be	1.78×10^{-3}	1.96×10^3	9.0122
Bi	3.13×10^{-4}	7.98×10^3	208.98
Ca	3.87×10^{-3}	1.89×10^4	40.08
Cd	1.12×10^{-4}	1.54×10^3	112.41
Ce	1.44×10^{-4}	2.46×10^3	140.12
Cr	1.18×10^{-2}	7.49×10^4	51.996
Cu	2.79×10^{-4}	2.16×10^3	63.546
Fe	1.01×10^{-2}	6.88×10^4	55.847
Hg	5.49×10^{-6}	1.34×10^2	200.59
K	2.00×10^{-1}	9.54×10^5	39.0983
La	1.15×10^{-4}	1.95×10^3	138.906
Li	6.81×10^{-5}	5.77×10^1	6.941
Mg	2.83×10^{-3}	8.39×10^3	24.305
Mn	3.66×10^{-3}	2.45×10^4	54.938
Mo	6.40×10^{-4}	7.49×10^3	95.94
Na	5.50	1.54×10^7	22.9898
Nd	1.20×10^{-4}	2.11×10^3	144.24
Ni	1.26×10^{-3}	9.02×10^3	58.70
P	4.98×10^{-2}	1.88×10^5	30.9738
Pb	3.27×10^{-4}	8.27×10^3	207.2
Sb	6.86×10^{-4}	1.02×10^4	121.75
Se	3.95×10^{-4}	3.81×10^3	78.96
Si	6.08×10^{-3}	2.08×10^4	28.0855

Table 2.4. (contd)

Waste Component: Chemicals	Total Feed: Concentration (M) ^(a)	Total Inventory: (kg) ^(b)	Molecular Weight (g/mol)
Ta	1.36×10^{-5}	3.00×10^2	180.948
Ti	9.55×10^{-5}	5.58×10^2	47.90
V	3.14×10^{-4}	1.95×10^3	50.9415
W	1.13×10^{-3}	2.53×10^4	183.85
Zn	1.03×10^{-3}	8.22×10^3	65.38
Zr	2.56×10^{-2}	2.85×10^5	91.22
CN ⁻	4.01×10^{-4}	1.27×10^3	26.0177
NH ₃	1.21×10^{-2}	2.51×10^4	17.0304
CO ₃ ⁻²	1.11×10^{-1}	8.13×10^5	60.0092
Cl ⁻	8.48×10^{-2}	3.67×10^5	35.453
F ⁻	7.14×10^{-1}	1.65×10^6	18.9984
SO ₄ ⁻²	7.16×10^{-2}	8.39×10^5	96.0576
NO ₃ ⁻	2.74	2.07×10^7	62.0049
NO ₂ ⁻	5.04×10^{-1}	2.83×10^6	46.0055
PO ₄ ⁻³	3.07×10^{-2}	3.56×10^5	94.9714
OH ⁻	1.15	2.39×10^6	17.0073

Waste Component: Radionuclides	Total Feed: Concentration (μ Ci/L) ^(c)	Total Inventory (Ci) ^(d)	Half-Life (years) ^(e)
³ H	5.07	6.19×10^2	12.3
¹⁴ C	2.00	2.44×10^2	5730
⁶⁰ Co	2.73×10^1	3.33×10^3	5.27
⁶³ Ni	1.19×10^2	1.45×10^4	100
⁷⁹ Se	3.0	3.66×10^2	6.5×10^4
⁹⁰ Sr	1.29×10^4	1.57×10^6	29.1* (28.5)
⁹⁵ Zr	1.73×10^3	2.11×10^5	0.1752 (64 day)

Table 2.4. (contd)

Waste Component: Radionuclides	Total Feed: Concentration ($\mu\text{Ci/L}$) ^(c)	Total Inventory (Ci) ^(d)	Half-Life (years) ^(e)
⁹⁴ Nb	1.30×10^{-3}	1.59×10^{-1}	2.00×10^4
⁹⁵ Nb	1.78×10^3	2.17×10^5	0.1752 ^(f) (64 day)
⁹⁹ Tc	5.17×10^1	6.31×10^3	2.13×10^5
¹⁰³ Ru	1.29×10^2	1.57×10^4	0.1076 (39 day)
¹⁰⁶ RuRh ^(h)	1.84×10^3	2.24×10^5	1.020
¹¹³ Sn	1.78×10^2	2.17×10^4	0.31485 (115 day)
¹²⁵ Sb	5.41×10^2	6.60×10^4	2.73
¹²⁶ Sn	9.1	1.11×10^3	1.0×10^5
¹²⁹ I	1.2×10^{-1}	1.46×10^1	1.57×10^7
¹³⁴ Cs	3.19×10^2	3.89×10^4	2.07
¹³⁵ Cs	0.69	8.42×10^1	2.3×10^6 * (3.0×10^6)
¹³⁷ Cs	1.32×10^5	1.61×10^7	30.2
¹⁴⁴ CePr ^(h)	1.55×10^3	1.89×10^5	0.7803 (285 day)
¹⁵² Eu	4.08	4.98×10^2	13.5* ^(e)
¹⁵⁴ Eu	1.49×10^2	1.82×10^4	8.59* (8.8)
¹⁵⁵ Eu	1.67×10^2	2.04×10^4	4.71* (4.96)
²²⁶ Ra	3.0×10^{-6}	3.66×10^{-4}	1600
²³⁰ Th	2.4×10^{-3}	2.93×10^{-1}	7.54×10^4
²³⁴ U	3.37×10^{-1}	4.11×10^1	2.454×10^5
²³⁵ U	1.97×10^{-2}	2.40	7.037×10^8
²³⁸ U	7.94×10^{-2}	9.69	4.468×10^9
²³⁷ Np	4.39×10^{-1}	5.36×10^1	2.140×10^6
²³⁸ Pu	1.59×10^{-1}	1.94×10^1	87.7

Table 2.4. (contd)

Waste Component: Radionuclides	Total Feed: Concentration ($\mu\text{Ci/L}$) ^(c)	Total Inventory (Ci) ^(d)	Half-Life (years) ^(e)
^{239/240} Pu ⁽ⁱ⁾	2.59	3.16×10^2	2.41×10^4
²⁴¹ Pu	8.90	1.09×10^3	14.4
²⁴² Pu	1.57×10^{-5}	1.92×10^{-3}	3.75×10^5 * (3.763×10^5)
²⁴¹ Am	2.33×10^1	2.84×10^3	433
²⁴³ Cm	4.14×10^{-2}	5.05	29.1* (28.5)
²⁴⁴ Cm	5.28×10^{-2}	6.44	18.1

- (a) Total feed values are as they appear in Appendix E (from Hendrickson and Conner 1993).
- (b) Total inventory in kilograms of chemical was generated by multiplying total feed concentration by waste volume (1.220×10^8 L) and by molecular weight, and then converting from grams to kilograms.
- (c) Total feed values are as they appear in Appendix E (from Hendrickson and Conner 1993). Inventory estimates of some radionuclides changed by less than 2% between the start and end of modeling due to correction of rounding errors in the inventory estimation. The inventory of europium-152 changed significantly but is negligible in all cases due to its short half-life. In all cases, the final inventory used in the central compliance case is shown.
- (d) Total inventory in curies of radionuclide was generated by multiplying total feed concentration by waste volume (1.220×10^8 L) and converting μCi to Ci units.
- (e) Half life values used in the transport simulations are from Browne, Firestone, and Shirley (1986). Half-lives marked with an asterisk are from Walker, Parrington, and Feiner (1989). The Walker et al. half-lives superseded the Browne et al. values for simulation of the central compliance case. Other compliance cases and sensitivity cases used the Browne et al. half-life value provided in parenthesis. The Walker et al. values are used in Appendix E. A correction to the europium-152 half-life from 1.6 years to 13.5 years was made after initial simulations had been performed.

Table 2.4. (contd)

Waste Component: Radionuclides	Total Feed: Concentration ($\mu\text{Ci/L}$) ^(c)	Total Inventory (Ci) ^(d)	Half-Life (years) ^(e)
(f) Niobium-95 is modeled with the half-life of its parent, zirconium-95, so it is not decayed away too rapidly; Browne, Firestone, and Shirley (1986) show a decay half life of 3.61 days for niobium-95 and Walker, Parrington, and Feiner (1989) show a value of 35 days.			
(g) Europium-152 half life shown, 1.600 years, is for a metastable state; Browne, Firestone, and Shirley (1986) show a value of 13.33 years for the more stable state, and Walker, Parrington, and Feiner (1989) show a value of 13.5 years.			
(h) Radionuclide pairs are in secular equilibrium. Activity shown is total for the parent. Half-life is shown for parent only.			
(i) The radionuclide pair $^{239/240}\text{Pu}$ is difficult to distinguish and, therefore, is shown as a lumped pair. The activity shown is total for the pair. The half life is for ^{239}Pu , the isotope with the longer half life.			

defined by this Order." High-level waste is defined as "the highly radioactive waste material that results from the reprocessing of spent nuclear fuel, including liquid waste produced directly in reprocessing and any solid waste derived from the liquid, that contains a combination of transuranic waste and fission products in concentrations requiring permanent isolation." Transuranic waste is defined as "without regard to source or form, waste that is contaminated with alpha-emitting transuranium radionuclides with half-lives greater than 20 years and containing greater than 100 nCi/g at the time of assay. From the perspective of radionuclide concentration, the low-level wastes to be grouted would be classified as Class C waste under criteria established by the NRC for commercial wastes (10 CFR 61). If the cesium-137 were removed, the waste would be designated as a Class B waste because of strontium-90 concentrations. All other radionuclides are at concentrations below Class A limits.

The Grout Disposal Facility has been designed to meet RCRA requirements for surface impoundments and landfills because of the chemical nature of the wastes to be disposed in the subsurface vaults. The waste is characteristically corrosive because of its hydroxide concentration. The hydroxide concentration is high enough to cause the pH to exceed the corrosivity limit of 12.5; therefore, the waste is classified as corrosive by the criteria of WAC 173-303-090(6). It is also characterized as TCLP (toxic characteristic leach procedure) toxic because of its concentrations of chromium, lead, cadmium, and silver. The concentrations of these materials exceed the designation limits of 40 CFR 261, Appendix II, for TCLP toxicity. In addition, the waste is characterized as toxic because of the high concentrations of nitrite and hydroxide ion.

2.3 Waste Feed Characterization

All waste feed materials will be characterized to ensure they meet all requirements for processing in the Grout Treatment Facility and will produce a grout waste form that is acceptable in grout formulation criteria. Waste determined to be unacceptable will be returned for additional processing or treatment. This section discusses the waste types that will be processed, the objectives for feed characterization, the sampling strategy for characterizing the waste feed for a grout campaign, and the specific activities to characterize the waste feed in a double-shell tank.

2.3.1 Waste Sources

As described earlier, the waste to be processed at the Grout Treatment Facility originated from various operating units across the Hanford Site. The grout waste feeds include DSSF, phosphate-sulfate waste (PSW), and the low-level waste fraction resulting from pretreatment of the Hanford Site high-level and TRU wastes. The contents of each double-shell tank are expected to be different from other tanks even though they contain the same type of waste, such as DSSF. The waste will be processed directly at the Grout Treatment Facility or, if the radiogenic heat loading is too high, dilute waste or water will be added before grouting.

2.3.2 Objectives for Feed Characterization

Feed characterization is conducted to determine if a batch of waste is acceptable for processing at the Grout Treatment Facility and for disposal in grout vaults. Feed acceptance criteria include the following.

- The waste composition must fall within the envelope for which an acceptable grout formulation exists.
- The waste must not generate so much radiogenic heat that the waste form temperature exceeds limits established by laboratory testing.
- The grouted radioactive waste must be within the Class C limits for low-level waste identified in low-level waste 10 CFR 61.
- The "characteristic" and "listed" constituents in the grouted waste must be shown to comply directly with land disposal restriction requirements of RCRA.

2.3.3 Overall Sampling Strategy

Two 1,000,000-gal, underground, double-shell tanks (Tanks 102-AP and 104-AP) have been designated as waste feed tanks for the Grout Treatment Facility. Before operations begin, these tanks will be equipped with mixer pumps to assure that the waste contents will be well agitated.

Before its transfer to a feed tank, the low-level mixed waste in a "candidate" tank is sampled and characterized. The data are used for feed formulation testing and assuring that the waste to be transferred would most likely be acceptable for grouting. Also, if the data indicate that the heat generation rate of the waste might be too high, thus requiring blending with dilute waste or water, a blending factor is calculated based on the radioactivity of the waste. If blending is required, the dilute waste is also characterized before its transfer to a feed tank.

The candidate waste, and any added dilute waste or water, is transferred to the feed tank. The contents are then agitated using the mixer pump. The waste is then sampled and the samples sent to a laboratory for analysis. The results of the feed tank characterization and testing are transmitted to the State of Washington Department of Ecology for review and the U.S. Environmental Protection Agency (U.S. EPA) and the NRC for information. Figure 2.26 depicts the overall sampling approach.

2.3.4 Characterization of a Feed Tank

Characterization of a 1,000,000-gal double-shell tank containing grout waste feed involves taking samples, analyzing the samples, preparing a data package, and reporting the data.

2.3.4.1 Sampling

Subsequent to transferring waste material into a waste feed tank, the tank is administratively isolated to prevent inadvertent transfer of material into the tank. This isolation process allows the tank to be sampled and completely characterized on a batch basis before starting a grout campaign.

S9211085.11

Figure 2.26. Overall Waste Feed Sampling Strategy

The mixer is used to agitate the contents of the tank. Furthermore, a sampling scheme, developed according to the guidance contained in the EPA's SW-846 manual (U.S. EPA 1986), allows accurate determination of the waste characteristics even if the waste is nonhomogeneous. As each new batch of material is received in a feed tank, a new sampling plan is prepared to eliminate any sampling bias from one tank to the next.

2.3.4.2 Analysis

The samples are analyzed for radionuclides and for organic and inorganic chemicals. Organic and inorganic analyses are conducted according to the EPA SW-846 procedures whenever possible. Some deviations in the sample preparation and analysis procedures are expected because the samples are radioactive.

The analytical laboratories have approved analytical procedures for most of the common radionuclides measured for waste characterization. The radiochemicals to be analyzed include tritium, carbon-14, technetium-99, strontium-90, niobium-94, cesium-137, iodine-129, plutonium, uranium, curium-242/244, neptunium-237, selenium-79, cobalt-60, americium-241, and ruthenium-106. Hazardous metals (i.e., arsenic, barium, cadmium, lead, mercury, selenium, and silver) and other inorganic constituents that may affect feed processability or product integrity (i.e., sodium, phosphate, sulfate, nitrate, and ammonia) are analyzed mainly through the use of the inductively couple plasma spectrophotometry and ion chromatography.

2.3.5 Characterization of a Candidate Tank

As discussed previously, the contents of a candidate tank are characterized to obtain preliminary information regarding feed acceptability. For this reason, the extent of characterization of a candidate tank is less than that performed for a feed tank. The sampling and analytical methods are basically the same; the exception is that fewer samples may be taken. Also, a complete data package and full validation are not required.

2.3.6 Waste Characterization Summary

All waste feed materials and candidate materials are characterized for chemical and radiological constituents to ensure they meet feed acceptance criteria for grout processing and waste form quality. Preliminary characterization is performed on candidate tanks after agitation with mixer pumps to obtain representative samples of tank contents. The preliminary data is used to determine if diluting or other processing is required before transfer to the grout waste feed tank. Feed tank contents are sampled and analyzed and the results reviewed by Ecology before grouting. Thus, several check points exist to ensure that an acceptable grout waste form with a known waste inventory will be placed in the vaults.

2.4 Characteristics of Grout

This section describes the grout waste form, the grout processing and placement operations, and the Grout Disposal Facility. The role of cementitious components in grout is discussed, along with formulation approaches, because waste feed composition will vary from tank to tank and the grout formulation will be tailored for each waste type. All formulations will include some or all of the same cementitious components, but these will be used in different proportions to meet performance and operational criteria for grouts made with specific waste types. In addition, all formulations must meet minimum criteria for acceptance that will be verified by extensive testing before placement. All 33 vaults will be filled with similar grouts, but by adjusting the formulation for each waste feed, minimum acceptance criteria (see Section 2.4.2) will be met or exceeded. A summary of waste containment mechanisms in grout is provided along with source term concepts that will be used for flow and transport modeling.

2.4.1 Components of Grout

Grout is prepared by mixing aqueous low-level waste with a preblended mixture of dry cementitious materials that react with the waste solution to produce a solid waste form. While specific waste streams will vary in composition, all will be characterized by high nitrate, hydroxide, and sodium concentrations. The slurry formed by mixing dry blend materials with the waste cures to form a solid product as a result of hydration reactions between the cementitious components of the dry blend and the aqueous fraction of the waste. The dry blend components are type I-II portland cement, class-F fly ash, ground blast furnace slag, attapulgitite-150 drilling clay, and Indian red pottery clay (an illitic clay), but these are not necessarily all used together in a specific grout formulation. A separate formulation will be developed for each waste feed to meet processing requirements and product characteristics such as long-term leachability and waste form stability. The following paragraphs describe the dry blend components and their function in the formulation.

2.4.1.1 Portland Cement

This material is a hydraulic cement composed dominantly of calcium silicates and calcium aluminates which react directly with water through hydration reactions to form both crystalline and amorphous hydration products. The hydration products provide the adhesive characteristics of cement that lead to desirable mechanical properties of hydrated cement-bearing materials. The portland cement used in the Hanford Site grout formulations is composed primarily of tricalcium silicate, Ca_3SiO_5 (55%); dicalcium silicate, Ca_2SiO_4 (22%); calcium aluminoferrite, $\text{Ca}_4\text{Al}_2\text{Fe}_2\text{O}_{10}$ (16%); and tricalcium aluminate, $\text{Ca}_3\text{Al}_2\text{O}_6$ (1%). Generalized reactions commonly used to express the hydration reactions of these materials usually are given as follows with the understanding that detailed specific reactions can be more complicated (Lea 1971).

In both cases, a hydrated calcium silicate with a lower Ca/Si ratio than the unhydrated material is formed along with calcium hydroxide. The calcium hydroxide generally accounts for the high pH in cement fluids and is also available for further reactions with other silica sources to form additional hydrated calcium silicates and to react with calcium aluminates according to the following possible expressions:

Hydraulic cement is the most reactive material in the dry blend and is required to initiate some of the hydration reactions of the other dry blend components. Typically, the reaction rate of cements is controlled by particle size or additives. The heat generated by calcium silicate reactions is generally above 100 cal/g for tricalcium silicates and about half that value for dicalcium silicates.

2.4.1.2 Blast Furnace Slag

This class of materials is sometimes referred to as latent hydraulic cements because they require activation to undergo hydration reactions. Once activated, these materials can react with water. Blast furnace slag is generally higher than portland cement in the oxides of aluminum, silica, and iron relative to those of calcium, magnesium, and sodium. Activation can be accomplished by many compounds if the compounds increase the pH of the aqueous phase in contact with the slag. Thus, sodium and calcium hydroxides are good activators. Both the portland cement and the waste solution itself can be activators for blast furnace slag in grouts because they yield calcium and sodium hydroxides, respectively. These materials increase the solubility of the silica-rich glass portion of the slag, promoting reactivity. Thus, the rate of slag reaction is dependent on its glass content. Good blast furnace slags generally have glass contents in the 85% to 90% range or higher. The heat of hydration generated by blast furnace slag is generally less than that for portland cement.

2.4.1.3 Fly Ash

This material is a pozzolanic material and is not hydraulic by itself. (It does not react with water by itself but will react with a dissolved hydroxide.) It will react with calcium hydroxide to form calcium silicate hydrates, which are the primary binder phases in silicate-based cements. Fly ash provides a source of

silica for the calcium hydroxides generated from the hydration of calcium silicates in portland cement as described above. A generalized reaction can be written as follows:

where the calcium-to-silica ratio in the calcium silicate hydrate can vary from about 0.83 to 1.7, depending on the relative amounts of reaction and extent of reaction.

The reactivity of pozzolans depends primarily on the amount of finely divided amorphous silica present. The composition and thus the reactivity of fly ash depends to a large extent on the type of coal the fly ash was derived from. Class F fly ash used in the grout formulations is typically that formed from the combustion of bituminous coal. The presence of pozzolans in cementitious blends tends to reduce permeability and produce a more durable product than with portland cement alone.

2.4.1.4 Clay

The clays used in grout formulations primarily function as suspending agents to support processing requirements by inhibiting separation of slurry constituents during pumping. The two clays used are attapulgite and Indian red pottery clay, an illitic clay. The illitic clay has a higher cation exchange capacity (10-40 meq/100 g) than attapulgite (3-15 meq/100 g) and can function secondarily as a sorbent for some ionic waste constituents such as cesium. Attapulgite has very little sorption capability. The idealized structural formula for attapulgite is $(\text{OH}_2)_4(\text{OH})_2\text{Mg}_5\text{Si}_8\text{O}_{20} \cdot 4\text{H}_2\text{O}$ with a structure based on double silica tetrahedral chains that results in a fibrous texture. Illitic clays can be considered as poorly crystallized micas and can be represented by the muscovite mica structural formula $(\text{OH})_4\text{K}_2(\text{Si}_6 \cdot \text{Al}_2)\text{Al}_4\text{O}_{20}$ with a slightly higher Si/Al ratio and lower K content than micas. As a result, natural illite particles tend to be small, on the order of 1 to 2 μm or less (Grim 1968).

2.4.2 Grout Formulation

The general requirements for grout formulation are based on three categories of criteria: 1) regulatory requirements--those required for local, state, and federal technical and environmental regulations and recommendations; 2) process requirements--those required to safely and economically process and place grout within the vault; and 3) other requirements--those required to produce a better product or to improve processing. These criteria are described in detail in Riebling and Fadeff (1991).

A specific grout formulation using some or all of the above dry materials will be developed for each type of waste stream to be grouted. Regardless of the specific formulation, the dry blend components and proportions selected to produce the grout slurry must meet both processing and product requirements (Riebling and Fadeff 1991). The processing requirements include limits on slurry critical flow rates, cure times, the amount of free-standing liquids developed, and the heat generated during curing.

Product formulation requirements include 28-day compressive strength determinations, leach index limits, TCLP toxicity limits, volume changes, and time-temperature effects on microstructural stability. The amount and type of dry materials along with waste loading can be adjusted for each waste stream to meet these requirements. The selected formulation is then evaluated and verified by both laboratory- and pilot-scale tests before adoption for a given waste stream type. Table 2.5 lists the composition of the dry blend materials. These materials influence the bulk composition of grout and the pore fluid chemistry.

In addition to the influence of dry blend mixture proportions and waste loading, curing conditions also have a strong influence on grout product properties such as compressive strength and leachability. Long curing times at elevated temperatures result in undesirable strength and leach index properties for grouts formed with most high-nitrate waste streams. This apparently occurs because the higher temperature microstructure can lead to coarser grain size, larger average pore size distribution, and salt precipitation. Curing temperatures are thus partly controlled by using more pozzolanic materials in the formulation instead of portland cement and limiting the total aluminum content. In addition, restrictions are placed on storage time (usually a few days) for dry blend mixtures, particularly those containing clay minerals with relatively high amounts of adsorbed and pore water that can react with hydraulic cements. In practice, the dry materials are blended with waste immediately before mixing to form the grout slurry. Some examples of grout formulations and waste loading used for Hanford Site grouts are given in Table 2.6. Because of variations in specific grout formulations and unknown formulations for future waste streams, grout properties used in this performance assessment will be based on the criteria

Table 2.5. Compositions of Representative Grout Dry Blend Materials, Wt%

Oxide	Portland Cement	Fly Ash Class F	Slag	Attapulgit	Indian Red Pottery Clay (Illite)
Al ₂ O ₃	2.96	23.94	13.4	8.70	19.40
B ₂ O ₃	0.06	0.45			
BaO	0.09	0.16	0.12	0.02	0.06
CaO	63.20	8.04	43.4	5.30	0.68
Fe ₂ O ₃	4.61	6.20	0.38	2.80	6.50
K ₂ O	0.60	0.60	0.89	0.80	3.30
MgO	0.43	1.80	5.62	9.00	1.26
Na ₂ O	0.32	3.02	0.40	0.10	0.15
P ₂ O ₅		0.70		0.80	
SiO ₂	23.00	50.80	33.3	53.00	61.00
SO ₃	3.32	0.33			
SrO	0.04	0.28	0.08	0.37	1.10
TiO ₂	0.23	3.67	1.08	0.37	1.10
Total	98.86	100.19	99.69	81.26	94.55

Table 2.6. Representative Grout Formulations

Dry Blend Materials	Phosphate/ Sulfate Waste	DSSF ^(a) (Alternate)	DSSF (Current Formulation)
Portland Cement	41	6	20.7
Fly Ash	40	47	68.3
Slag		47	
Limestone Flour			
Attapulgite	11		11
Indian Red Pottery Clay	8		
Dry Blend/Waste Mix Ratio	7-7.5 lb/gal	8-9 lb/gal	8.4 lb/gal

(a) Double-Shell Slurry Feed.

described in the Grout Formulation Standard Criteria Document (Riebling and Fadeff 1991). This document specifies limiting properties applicable to all grout formulations. Table 2.7 lists some of these criteria.

Table 2.7. Partial List of Grout Formulation Criteria (after Riebling and Fadeff 1991)

Leachability Index	>6.0 for total nitrogen
Toxicity	TCLP on 28-day cure samples must meet WAC 173-303 specifications for eight toxic metals.
Free-Standing Liquid	<0.5% by volume at cure
Unconfined Compressive Strength	>500 lbf/in. ²
Temperature Rise	Maximum adiabatic heat of hydration temperature <90°C.
Slurry Cure Time	Slurry must cure and solidify within 28 days.
Time-Temperature Effects	Exhibit microstructural stability beyond initial cure period as reflected by compressive strength and leachability.
Immersion	No evidence of cracking, spalling, or bulk disintegration after immersion in water for a minimum 90-day period.
Expansion/Contraction	No expansion/contraction after initial cure.

Test results for nitrate leachability and compressive strength for both laboratory-prepared and pilot-plant core samples using the current grout formulation are given in Table 2.8. The results are indicative of the properties expected in the first campaign of grout pouring for the first four vaults. The lower leach indices for the pilot-scale cores are most likely related to an increase in surface area available for leaching caused by air entrainment in the pilot-scale grout. The viscosity of the grout entering the pilot-scale mold was substantially higher than in laboratory-prepared samples because of shear thickening that occurred during pumping. For comparison, the leach index used in the performance assessment is 6.0.

2.4.3 Grout Waste Containment and Source Term Concepts

Before being mixed with dry blend materials, waste streams typically contain about 25 wt% to 27 wt% salts. A small degree of salt concentration occurs because of water consumed in hydration reactions with the dry blend. The amount of hydration water can be approximated if it is assumed that none of the nitrate is lost from the liquid waste during the hydration process. Beginning with a synthetic DSSF waste containing 185 g/L nitrate, Lokken et al. (1992) extracted pore fluids from grouts made with the DSSF 47,47,6 formulation (Table 2.6) that were cured between 65°C and 95°C for up to 6 months. After 6 months, pore fluids obtained with a punch and die apparatus averaged about 200 g/L nitrate. This suggests that about 8% to 10% of the water is used in hydration reactions.

The waste-to-dry blend mix ratio is sufficient to expect that the pores in the solidified grout are volumetrically saturated with fluid plus salts. Only the more soluble salts and contaminants are expected to be primarily in the pore fluids. Other contaminants can be incorporated in hydration products as solid solution components or interstitial compounds. Also, contaminants may precipitate directly as oxides, hydroxides, silicates, sulfates, etc. Contaminants whose concentrations in the pore fluid are solubility controlled or otherwise retarded by reaction with hydration products will be released at a slower rate than more soluble components. While pore fluid compositions are not evaluated directly in this performance

Table 2.8. Nitrate Leachability and Compressive Strength for Laboratory-Prepared and Pilot-Scale 106-AN Grout Samples (Lokken et al. 1993)

	Nitrate Leach Index ^(a)		Compressive Strength, psi	
	Lab Samples	Pilot Scale	Lab Samples	Pilot Scale
Mean	7.18	6.37	1235	899
Std. Dev.	0.22	0.16	373	203
Min	6.82	5.99	712	602
Max	7.55	6.61	1992	1438

(a) The leach index is defined as $-\log_{10}$ of the effective diffusion coefficient expressed in cm^2/s , with the concentration driving force defined in the bulk grout. A value of 6.0 is used in this performance assessment.

assessment, differences in release behavior for individual species are determined experimentally through ANS 16.1 leach tests. Effective ionic diffusivities determined from leach tests on bulk grout samples are based on initial waste loading inventories and implicitly include retardation mechanisms such as precipitation and sorption. As will be discussed in more detail in Chapter 3, specific groups of radionuclides and chemical species are assigned grout retardation factors based on these experimentally determined effective ionic diffusivities. Contaminant release is then considered to occur by advective flow through porous grout, with effective diffusivities from grout controlling concentrations in the flowing water. The experimental effective ionic diffusivities determined on bulk samples are corrected for the volume fraction of pores in the grout, as will be discussed in Chapter 3.

2.4.4 Grout Waste Form Summary

Specific grout formulations will be tailored for individual feed compositions, but all formulations will contain the same cementitious components and must meet minimum acceptance criteria before placement. For convenience and conservativeness, grout properties used in this performance assessment will be based on these minimum criteria. It is assumed that the waste inventory contained in grout ultimately will be released by advection, but relative release rates will be based on retardation factors determined by experimental release rate results from ANS 16.1 leach tests.

2.5 Waste Treatment and Disposal: Waste Form Processing

This section summarizes the processing subsystems that compose the Grout Treatment Facility where liquid waste materials are combined with cementitious dry blend materials to form the grout slurry to be pumped into underground vaults. These components include the Dry Materials Facility, the Feed Transfer System, the Grout Processing Facility, and the Grout Disposal Facility. The Grout Processing Facility and four vaults under construction are shown in Figure 2.27; a schematic of the Grout Treatment Facility components is shown in Figure 2.28.

The Dry Materials Facility, which is centrally located in the 200 East Area of the Hanford Site, receives dry cementitious materials by truck or rail car for storage and subsequent blending. The blend proportions are established as a specific grout formulation for a specific waste feed through the grout formulation process described in Section 2.4.2. After testing for proper proportions, the dry material blend is trucked to the Grout Processing Facility and loaded into a storage bin.

The Feed Transfer System is composed of two designated double-shell tanks located in the 200 East Area AP Tank Farm and the underground encased transfer line to the Grout Processing Facility. Each tank has a capacity of 4,126 m³ (1,090,000 gal) and includes a pump for mixing and transferring the wastes. After mixing, samples are withdrawn from the tank for confirmatory chemical and radiochemical analyses and to verify acceptable grout processing and product properties by preparing hot grout samples.

Figure 2.27. Aerial View of the Grout Treatment Facility Location

S9211085.12a

Figure 2.28. Grout Treatment Facility

The Grout Processing Facility, which is the primary element of the Grout Treatment Facility, includes the control room for the remote processing operation and the below-grade, isolated, covered mixer module. Waste feed from one of the two feed tanks is transferred to the mixer module via an underground encased line. In the mixer module, the waste is mixed with dry blend materials to form a grout slurry. The slurry is pumped through underground encased lines to the Grout Disposal Facility vault(s), where it cures to form a solidified grout monolith.

The Grout Disposal Facility is composed of large underground near-surface, steel-reinforced, asphalt-lined concrete vaults with an approximate volume of 6,000 m³ (1,585,000 gal). Major components of the disposal system include the vaults and catch basin, asphalt barrier, RCRA cover, and a permanent isolation barrier. Details of these components of the disposal facility are described in Section 2.6. Figure 2.29 shows the vault layout and proposed filling schedule. Although 44 vaults are shown in the plan, only 33 of these are expected to be filled on the basis of current waste volume projections. The Grout Disposal Facility also includes associated grout slurry transfer lines; excess water return lines; a

Figure 2.29. Aerial View of the Grout Treatment Facility Showing the Location of 44 Vaults as Forecast in 1990;
Current Volume Estimates Would Yield 33 Units

portable instrument house for sensing grout temperature, grout level, and sound transmission properties; and a vault exhauster for maintaining negative vault pressure and for cooling grout during vault fill and cure operations.

2.6 Grout Disposal Facility

This section describes the engineered components of the grout vault system, including the vault structure and associated barrier systems to be placed above the vaults. Descriptions of the steel-reinforced concrete vaults and catch basins are included along with the asphalt barrier which surrounds the concrete vault and the RCRA cover, which will cover all vaults in the Grout Disposal Facility. Specific hydraulic properties needed for flow and transport modeling of the system's engineered components are discussed in Chapter 3.

2.6.1 Concrete Vault and Catch Basin

Thirty-three vaults are required to dispose of waste currently identified for processing by the Grout Treatment Facility. Figures 2.30 and 2.31 show the conceptual design of the vaults that will receive the grouted waste. Internally, each vault will be 37.6-m long, 15.4-m wide, and 10.4-m deep (123.5 x 50.5 x 34 ft). The total capacity of the vault, full to the top, is 6.0 million liters (1.59 million gallons), which includes both the grouted waste and a 1.2-m (4-ft) thick grout "cold cap" of grout without waste. The vault walls and floor are constructed of cast-in-place reinforced concrete and the roof is composed of precast cover panels. The vaults are designed to withstand both the surcharge loading of the earth backfill and the hydrostatic loading from the grout slurry. The vaults are designed to withstand an earthquake with a 0.25 G horizontal and 0.17 G vertical acceleration (U.S. DOE 1990b, Section 2.4.2). The concrete mix design includes a slag component, which improves long-term durability with a low water/cement ratio, improving strength. The minimum compressive strength of this mix is 4,500 lb/m² (31.03 MPa). Wall thickness ranges from 0.30 m (1 ft) at the top to 1.07 m (3.5 ft) at the bottom. Steel water stops are installed between pour sections of the vault.

The roof of the vault is made of 31 precast, prestressed concrete cover blocks (panels) laid across the width of the vault. Each panel is 1.22-m (4-ft) wide, 16.0-m (52.5-ft) long, and 0.66-m (2.2-ft) thick. Gaps between adjacent panels are filled with a cement grout and the panels are topped with a concrete layer that slopes from 20.3-cm (8-in.) thick at the center of the vault to 5.1-cm (2-in.) thick at the edge.

Each vault will contain up to 5.3 million liters (1.4 million gallons) of grouted waste, corresponding to a fill level of 9.1 m (30 ft). The contents of one grout feed tank--3.78 million liters (one million gallons) of waste--will result in 4.9 to 5.3 million liters of grout. Following a minimum 30-day curing period, any liquid on the grout surface will be removed and returned to the waste tanks for grouting later. The remaining void space in the vault will be filled with a nonradioactive "grout cap." The cold cap provides additional support to the cover to prevent subsidence.

S:R001C064

Figure 2.30. Grout Disposal Facility--Grout Disposal Vault, Cutaway View

Figure 2.31. Grout Disposal Facility--Closed Vault Pair

The vaults are designed to meet RCRA requirements for double containment. The primary containment is the vaults and a 1.32-mm-(52-mil)-thick, asphalt-based sealant applied to the interior walls and floor of the vaults. Near the top of the walls, the thickness is increased to 1.9 mm (75 mil) to increase the crack-spanning ability of the sealant. The sealant is composed of an asphalt/naphtha mixture combined with polyisocyanate. The mixture forms an elastic, rubbery coating on the vault surfaces. The vault/liner system is tested for leaks before use, and any leaks are repaired. Therefore, the chances for leakage are low when the vault is filled with grout slurry and as the grout cures.

The secondary containment is provided by a catch basin beneath the vaults. The catch basin is constructed of reinforced concrete. Its major components are concrete with a minimum compressive strength of 31.0 MPa (4,500 lb in.²), Grade 60 reinforcing steel with a yield strength of 414 MPa (60,000 lb in.²), and ASTM A 36 (ASTM 1987) steel-plate water stops. The catch basin is lined with a 60-mil-thick high-density polyethylene (HDPE) flexible membrane liner that meets RCRA requirements.

To provide a drainage path and to support the weight of the vaults, the catch basin is filled with a washed small gravel to a thickness of 0.30 m (1 ft) near the edges and 1.2 m (4 ft) at the low point in the trough in the middle of the catch basin. A geotextile is laid over the gravel to prevent seepage of concrete

into the gravel during construction of the vault floor. A perforated steel collection pipe runs through the catch basin trough to a sump. The exterior walls of the vaults are surrounded by an HDPE drainage net and curtain. Insulation board is placed between the HDPE and the asphalt barrier described below. Should a leak occur in a vault, the leaking fluid would be directed by the HDPE drainage net to the catch basin and into the sump. The liquid level in the leachate collection system will be monitored for a minimum of 30 years after the vaults are filled, and any liquid collected will be removed for processing.

2.6.2 Asphalt Barrier

An asphalt barrier that completely surrounds the concrete vaults has been incorporated into the design of the grout vaults. The barrier is intended to retard the diffusion of contaminants to the soil column and the diffusion of water vapor from the soil to the grouted waste, and to provide a hydraulic barrier to infiltrating water. The asphalt barrier consists of a solid asphalt/aggregate pavement that is similar to a road pavement. However, the construction specification for the barrier requires less than 4% voids, rather than 8% to 10% voids as is typical for road pavement. The asphalt barrier is composed of 7.5 ± 5 wt% asphalt (16.2 vol%) and aggregate with a maximum sieve size of 5/8 in. and with 65% to 75% passing a #4 sieve (just under 1/4 in.). Generally, the aggregate size distribution for the asphalt barrier is similar to the gravelly sands of backfill soil. The asphalt barrier completely surrounds the vault and catch basin and is installed during construction. There is a minimum 1.0-m (3.3-ft) thickness of the asphalt barrier on the sides and top of each vault. Beneath the catch basins of the first four vaults, the barrier is composed of a 0.46-m- (1.5-ft-) thick layer of asphalt pavement on top of another 0.46-m minimum-thick layer of asphalt-coated gravel. All future vaults to be constructed will have a minimum 1-m- (3.3-ft-) thick layer of asphalt pavement surrounding the vaults, including the underside of the catch basin.

2.6.3 RCRA Cover

After they are filled with grout and the cold cap, the vaults will be closed in pairs to meet RCRA cover guidance for a lateral drainage layer. A cross section of the closure cover over a pair of vaults is shown in Figures 2.31 and 2.32. The cover design is based on the requirements of 40 CFR 264 and WAC 173-303-665(6).

Backfill soil will be placed between the vault pairs and gravel will be placed in contact with the asphalt barrier, forming a gravel layer above the vault. The gravel layer will have a 10% slope and provide a capillary break. All subsequent layers of the RCRA cover will also have a 10% slope. A 0.30-m- (1-ft-) thick "filter" sand layer will be placed immediately above the gravel. This sand drainage layer is designed as a granular filter to prevent infiltration of fines into the gravel layer. The particle size distribution is also selected such that any draining water will preferentially flow through the sand and not through the gravel. Next, a geotextile will be placed over the filter sand layer. This fabric will be used to prevent plugging of the sand layer by fine soil particles from cover layers above. The filter sand will be composed of clean sand and will provide additional protection for removing water that percolates through materials placed above it.

H9106018.2

Figure 2.32. Detail of Grouted Waste Disposal Vault with RCRA Cover

A water infiltration barrier composed of a mixture of selected excavation materials and imported bentonite clay (about 10% clay) will be installed over the geotextile. The function of this low-permeability layer is to minimize the infiltration of water through the cover because no credit is taken for the long-term integrity of the HDPE geomembrane above. The clay/soil mixture will be compacted in lifts to a saturated hydraulic conductivity of not more than 1×10^{-7} cm/s. This layer will be nominally 0.61-m (2-ft) thick and will be below the average frost depth.

An HDPE geomembrane will be placed over the bentonite/soil layer, again to minimize migration of fine materials through the cover. Another 0.30-m (1-ft) layer of cleaned drainage sand and geotextile will be placed above the geomembrane. The area will be backfilled with topsoil. The area will be graded so that the surface is sloped to drain, prepared for planting, and fertilized, seeded, and mulched. This action completes the RCRA barrier. At final site closure, a permanent isolation barrier and warning marker system (Section 2.7) will be placed over the Grout Disposal Facility.

2.6.4 Disposal Facility Summary

The development of the conceptual model and grid system discussed in Chapter 3 to model contaminant flow and transport from the vaults addresses the main components of the engineered system and their dimensions. The grouted waste and cold cap are considered together as the grout waste volume in developing the grid system. The reinforced concrete vault and the asphalt concrete barrier also are modeled explicitly. Other components used are the RCRA barrier, the gravel layer, and a permanent isolation barrier over the entire Grout Disposal Facility. Various geotextiles are considered short term and are not considered in modeling. The hydraulic properties assigned to specific engineered components for modeling purposes are presented and discussed in Chapter 3.

2.7 Permanent Isolation Barrier^(a)

Westinghouse Hanford Company and Pacific Northwest Laboratory are jointly developing and testing protective barrier and warning marker systems (Adams and Wing 1987). Permanent isolation barrier and warning marker systems use engineered layers of natural materials to create an integrated structure with redundant protective features. The emphasis of the work has been on the development of barriers and markers for above-grade (mounded barrier) application to existing waste sites where the soil profile should not be disturbed. However, the barrier design described in the performance assessment is also relevant and applicable to the Grout Treatment Facility. Figure 2.33 is a conceptual drawing of the permanent isolation barrier and warning marker system. The natural construction materials (e.g., fine soil, sand, gravel, riprap, clay, asphalt) have been selected to optimize barrier performance and longevity. The objective of the current design is to use natural materials to create a maintenance-free permanent isolation barrier and warning marker system that isolates wastes for a minimum of 1,000 years by limiting water drainage to near-zero amounts; reducing the likelihood of plant, animal, and human intrusion; controlling the exhalation of noxious gases; and minimizing erosion-related problems. The following list summarizes the design objectives for the barrier and marker system. The objectives are intended to be broad enough to encompass the various regulatory requirements for the types of wastes anticipated for near-surface disposal at the Hanford Site and other DOE sites in the arid and semiarid western United States.

- Functions in a semiarid to subhumid climate

(a) In April 1993 a new prototype design for the permanent isolation barrier was issued. It differs from the design described in Appendix F. Certainly, as data are gathered and the performance of the 1993 prototype is assessed, the design will be revised. Because one cannot assert that any design described here is final (i.e., because it will be constructed during site closure), it has been decided not to revise this text. The new prototype design is described in WHC (1993).

Figure 2.33. Conceptual Permanent Isolation Surface Barrier and Warning Marker System for an Above Grade Application

- Limits the recharge of water through the waste to the water table to near-zero amounts; a long-term annual average of 0.05 cm of water per year [i.e., a drainage rate of approximately 2×10^{-9} cm/s]
- Remains maintenance free by minimizing the likelihood of plant, animal, or human intrusion, and minimizing the likelihood of significant wind and water erosion of the barrier surface.

2.7.1 Barrier Design

The protective barrier and warning marker systems consist of a variety of different materials (e.g., fine soil, sand, gravel, riprap, asphalt, clay) placed in layers to form an above-grade mound or at-grade profile directly over the waste zone. Surface markers are placed around the periphery of the waste sites to inform future generations of the nature and hazards of the buried wastes (see Figure 2.33).

The protective barrier design consists of a fine-soil layer overlying other layers of coarser materials including sand, gravel, or basalt riprap (Figure 2.34). Each of these layers as listed in Table 2.9 serves a distinct purpose. The fine-soil layer acts as a medium in which moisture is stored until the processes of evaporation and transpiration can recycle excess water back to the atmosphere. The fine soil layer also provides the medium for establishing plants that are necessary for transpiration to take place. McGee Ranch silt loam is currently the fine soil of choice because it will create a favorable environment for containing the biological cycles in the upper portion of the barrier, thereby reducing biointrusion into the lower layers. The coarsest materials (i.e., successively coarser sand, gravel, and basalt riprap) that are placed directly below the fine-soil layer create a capillary break that inhibits the downward percolation of

Figure 2.34. Cross Section of a Conceptual Permanent Isolation Barrier and Warning Marker System

water through the barrier. The coarsest materials will also help to deter inadvertent human intruders from digging deeper into the barrier profile. A low-permeability layer placed in the barrier profile below the capillary break is included in the protective barrier design. The purpose of the low-permeability layer is to divert any percolating water that gets through the capillary break away from the waste zone, and to limit the upward movement of gases from the waste zone. The low-permeability material of choice is asphalt, which is hydrophobic (i.e., not wetted by water) and should be an excellent redundant barrier to recharge.

Natural construction materials (e.g., fine soil, sand, gravel, cobble, crushed basalt riprap, asphalt, clay) have been selected to optimize barrier performance and longevity. The need for a maintenance-free barrier necessitates the use of passive systems. Knowledge of how natural processes affect barrier performance has led to a design that passively meets design and performance objectives.

The protective barrier design accounts for the potential of wind erosion by incorporating gravel admix in the upper silt layer. The potential for deposition of wind-blown soils is now being addressed. However, while active dunes at the Hanford Site cover a significant portion of the Site, they are predominantly a fine sand. The majority of these dunes are vegetated to some extent. Recharge is expected to be low where vegetation is present (Gee et al. 1992), although recharge has not been measured directly on the dune areas. Presently, the more active and least vegetated dunes lie to the southeast of the facility adjacent to the Columbia River. Shallow-rooted vegetation is probably more suited than deep-rooted species to adapt to the dynamic active dune environment. As a result, infiltration and recharge at active

Table 2.9. Vertical Layering and Materials of the Protective Barrier

Layer Thickness	Description	Comment
2 m	McGee Ranch Silt Loam	The McGee Ranch silt loam will be placed in two lifts; 1.5 m of clean silt-loam soil will be placed immediately above the sand filter, then 0.5 m of silt mixed with pea gravel will be placed and shaped to the grade elevation of the site.
15 cm	Sand Filter	This sand will act as a hydraulic filter between the overlying silt and the underlying crushed rock gravel. A woven geotextile is to be installed between sand and silt layers.
30 cm	Gravel Filter	This crushed rock gravel filter will act as a hydraulic filter between the overlying fine sand filter and the underlying fractured basalt core of the barrier system.
50 cm	Basalt Riprap	The fractured basalt riprap is the primary capillary break in the isolation barrier system. This media is to have a minimum of fines in its grain size distribution to ensure a considerable open porosity. The physics of unsaturated water flow require water to nearly reach saturation in the silts overlying the sand filter before water will enter the sand, and to nearly reach saturation in the sand overlying the gravel filter before water will enter the gravel.
30 cm	Gravel	This gravel layer acts as a cushion between the basalt riprap and the asphalt. It ensures against damage to the asphalt during placement of the basalt.
15 cm	Asphalt	Asphalt is placed in two lifts to provide added assurance that adequate compaction is achieved. In addition, this ensures that preferential flow does not occur through single joints or localized areas of lower integrity (e.g., lower compaction or higher conductivity) in a single layer.

dune locations could be substantial fractions of the precipitation. However, the present south and south-east locations of the dunes downwind of the Grout Disposal Facility make it less probable that dune formation events will dominate in the future and more probable that wind erosion will dominate.

2.7.2 Summary of Barriers

The Grout Disposal Facility includes many barrier materials above the grout vaults. The first one is a gravel layer located between the asphalt barrier and the RCRA cover. The gravel layer and RCRA cover provide a capillary break and reduces moisture infiltration. The permanent isolation barrier will cover the entire Grout Disposal Facility above grade and is the final closure operation. The permanent isolation barrier is an additional capillary break that provides redundancy against excessive recharge and also provides protection from intrusion by plant roots or animals and intruders.

3.0 Analysis of Performance

This chapter describes the methods and data used in the analyses presented in this performance assessment. Sections 3.1 (Background) and 3.2 (Pathways and Scenarios) provide a general description of how releases may occur, which pathways the contaminants will follow in the environment, and how future inhabitants of the region will be exposed. Sections 3.3 (Source Term and Engineered System), 3.4 (Unsaturated and Saturated Sediment Pathway), and 3.5 (Codes and Modeling Approach) present the equations, data, codes, and models for the source region and the environmental and exposure pathways. Section 3.6 (Performance Assessment Methodology) presents the cases used to evaluate compliance and evaluate the sensitivity of analyses to specific design elements and model parameters. Interpretations presented in this chapter rely on the information presented in Chapter 2; however, data specific to the waste form and engineered structures are presented here. Results of the analyses described here are presented in Chapter 4.

3.1 Background

As described in Chapter 2, grout consists of aqueous low-level radioactive waste mixed with a blend of cementitious materials that react to produce a solid waste form. As illustrated in Figures 2.30 and 2.31, the Grout Disposal Facility is an engineered disposal system with multiple barriers. The top of the vaults will be approximately 5 m (16.4 ft) underground, and Resource Conservation and Recovery Act (RCRA) and permanent isolation barriers will overlay the entire Grout Disposal Facility.

Contaminants are released from the Grout Disposal Facility by their desorption and dissolution into the pore fluids in the grout monolith, and moved by advection and diffusion from the grout into the surrounding engineered and natural materials. Once out of the Grout Disposal Facility, contaminants are free to advect or diffuse in any direction. They can move upward by ionic diffusion under conditions of zero or extremely low recharge and downward by advection with recharge. Some contaminants in the unsaturated zone are sorbed to the sediments. Other contaminants are not sorbed and move with the recharge. As contaminants move downward toward the unconfined groundwater, relatively short-lived radionuclides decay within several thousand years to negligible concentrations.

Future exposures to contaminants from the Grout Disposal Facility are assumed to occur through numerous pathways. The primary pathway is transport with infiltrating water downward through the unsaturated zone and into the groundwater flowing beneath the facility. Once in the groundwater, contaminants can migrate and discharge to the Columbia River. People downstream of the Hanford Site are exposed by using river water for drinking, household needs, irrigation, and recreation. Another scenario postulates groundwater flow to a downgradient well. Exposures occur by using the groundwater for drinking water, to irrigate the gardens of a small community (80 people), to irrigate an individual family's garden, and to serve a small family farm. Another important exposure pathway is intrusion into the Grout

Disposal Facility during drilling and the subsequent exposures from contamination spread on the ground surface. Upward diffusion of radon and other radionuclides was considered as a potential exposure scenario, as was spread of contamination by flooding. Figure 3.1 illustrates the overall conceptualization of the transport and exposure pathways.

The flow of water around and through the Grout Disposal Facility, and the transport of contaminants away from the facility, will be three dimensional in nature. Thirty-three vaults will be affected by infiltrating water. In this performance assessment, a single vault was analyzed in a two-dimensional cross section to determine the movement of contaminants from the grout, through the engineered disposal system, through the unsaturated zone, and into the groundwater beneath the disposal site. The results of the single vault analyses were then extrapolated to 33 vaults. Centerlines between vaults were used to define the two-dimensional domain evaluated in the model. Because of the symmetry between pairs of vaults, the centerlines between vaults were defined to be vertical no-flow boundaries. These lines of symmetry imply that infiltrating plumes from the different vaults will not intersect. Figure 3.2 illustrates the two-dimensional cross section represented in the model. A model of the unconfined aquifer is used to estimate the travel time of contaminants transported through the groundwater and to the Columbia River. The most significant exposure pathways using groundwater to transport contamination occur over a fairly

S9409073.1

Figure 3.1. Overall Conceptual Model for the Grout Technology Performance Assessment

S9305096.5

Figure 3.2. Two-Dimensional Cross Section of Soil Profile

short distance within the aquifer [e.g., to a point 100-m (328-ft) downgradient of the facility, before the contamination is removed by a well supplying water for irrigation and domestic needs. Doses resulting from human exposure to radionuclides disposed in grout were calculated using an environmental dosimetry model which includes dosimetric and metabolic models recommended by the International Commission on Radiological Protection (ICRP).

Conversion of the results from the analysis of a single vault to the field of 33 vaults, and the total inventory, is achieved by linear scaleup of contaminant flux. The analysis of flow and transport within the vadose zone results in the calculation of a fractional release from the unit inventory in two-dimensions. This fractional release is then applied to the inventory for the entire vault field. The total contaminant flux is spread evenly over the waste management area as leachate or contaminant recharge to the unconfined aquifer. This approach implies that all vaults fail simultaneously. While simultaneous failure is unlikely, this approach is justified because the failure of vaults is expected to occur over a relatively short period of time.

3.1.1 Approach

The purpose of the analyses described in this document is to estimate exposure and incremental dose over time resulting from both mobile and sorbed radionuclides in the low-level waste inventory planned for disposal in grout. Simulations were conducted over hundreds to thousands of years to estimate long-term consequences and maximum exposure and dose. These long-term simulations include consideration of the timing of potential degradation of the engineered system. In all cases, conceptual models of the engineered and natural system were based on current understanding of the physical media (e.g., intact and degraded states of grout, concrete, asphalt, gravel, backfill soil) and knowledge of contaminant transport processes. Both the significance of different elements in the engineered and natural system and the sensitivities of performance estimates of model parameters provided indications of system performance.

The analysis strategy employed in this performance assessment can be best described as an evolving process. A large number of system components, modes of degradation, and degrees of model complexity and sophistication could be employed in analyzing grout disposal. However, computational resources, technical capabilities, and available data have defined the level of sophistication that can be used at this time. This performance assessment (the series of completed simulations) has evolved as part of a continuing effort to define and simulate a best estimate of the long-term performance of the engineered disposal system. However, defining a single best estimate, especially for the properties of degraded engineered components of the system, has proven difficult and may be impossible. Therefore, conceptualizations of the disposal facility and the surrounding environment were adopted for more sophisticated simulations while efforts continued toward defining a "best" estimate case. A phased

approach to the performance assessment of grout evolved. The most important components in the engineered system, the most sensitive parameters in process models, and the most significant combinations of component and parameter sensitivities were incorporated into more sophisticated case studies.

Initially, a central sensitivity case was developed to test codes and modeling concepts and provide the context for understanding the results of design and sensitivity cases. The design cases, which involved constant property assignments and perturbations to engineered components and model parameters, were used to examine the relative importance of design features in the engineered system. After establishing important design features, the relative sensitivities of different aspects of flow and transport phenomena were examined in a series of simulations termed "sensitivity cases." Based on knowledge gained from the design and sensitivity cases, a series of cases incorporating appropriate engineered features and process models was conceptualized. These cases were used to examine the potential significance of increasing levels in degradation over time. The effects of degradation on release were evaluated by making step changes to physical, hydraulic, and transport properties for those components of the engineered system that are likely to degrade and cause a greater rate of release. These step changes were examined in a series of simulations termed "compliance cases." The compliance cases provide the basis for comparison with performance objectives.

3.2 Pathways and Scenarios

This section begins with a brief discussion of the time periods of interest in the simulations, and the identification and screening of both transport and exposure pathways for the grouted wastes and their disposal location. That discussion is followed by a description of conceptual models for the release, transport, and environmental accumulation or exposure pathways. A final subsection briefly describes flow and transport process models and their parameters. The general descriptions of release, transport, and exposure models, and the related terminology, introduce the presentation of the source term and the process models and data for the engineered system, environmental pathways, and exposure scenarios.

3.2.1 Time Periods of Interest

Chapter 1 established the time periods of interest in terms of performance objectives for this performance assessment. Protection of the general public and groundwater will be evaluated for compliance to regulatory performance objectives for 1,000 years and programmatic performance objectives for 10,000 years. The requirements for intruder doses following either a single acute or continuous chronic exposure will be evaluated at 500 years after disposal.

Although long-term performance objectives are evaluated for compliance up to 1,000 and 10,000 years, nearly all simulations will be continued to peak concentration and/or dose. Many of the simulations involving transport in the unsaturated zone and groundwater require far beyond 10,000 years to reach peak concentrations in a downgradient well because of the relatively high integrity of the engineered disposal system, the slow release of contamination from the Grout Disposal Facility, and the slow

migration of contaminants through the unsaturated zone sediments. Many cases were simulated for several hundred thousand years. However, as simulations are continued beyond 10,000 years, there is increasing uncertainty associated with long-term integrity and degradation of the Grout Disposal Facility and conceptualization of the flow system. Thus, results beyond 10,000 years are included for completeness, but not for comparison with performance objectives.

3.2.2 Pathway Identification and Screening

This section describes the identification and screening of pathways for transport and exposure. Transport pathways are described first, followed by descriptions of exposure pathways. Transport pathways cover the release and transport of contaminants from the Grout Disposal Facility through the soil and groundwater to either a downgradient well or the Columbia River. Exposure pathways refer to distribution and accumulation of radionuclides in the environment and food chain used to determine human exposures. Exposure pathway screening also included exposures to radionuclides from direct intrusion into the facility.

3.2.2.1 Transport Pathways

This proposed disposal places low-level radioactive wastes in buried engineered structures. The upper surface of the waste is to be at least 5 m (16.4 ft) below the land surface. The Grout Disposal Facility is located on the 200 Area plateau adjacent to the 200 East Area. At this location, the current facility design places wastes 60 to 70 m (200 to 230 ft) above the water table. Clearly, environmental transport must involve movement, either up or down, in the unsaturated sediment profile. Throughout the Hanford Defense Waste Environmental Impact Statement (HDWEIS) (U.S. DOE 1987), the significant transport pathway was downward migration through the unsaturated zone and to the groundwater. The downward pathway has therefore been included as a transport pathway in this performance assessment. Two alternate routes of upward transport have also been identified: upward migration of radon in a gaseous phase and upward migration of the inventory by diffusion (assuming infiltration is negligible) in the liquid phase. The potential lateral movement of wastes in any substantial or continuous way has not been analyzed because there is no known geologic structure underlying the Grout Disposal Facility that would divert a release laterally to a major extent, or lead to an early or "short circuited" exposure. Accordingly, the following transport pathways were identified and evaluated:

- Advection and diffusion of contaminants through the unsaturated zone to the unconfined aquifer
- Upward diffusion of contaminants through the soil water to the land surface
- Upward diffusion of radon through the gas phase to the land surface.

The release of contaminants from the grout and the subsequent transport of those contaminants to either a groundwater well or the Columbia River was analyzed in two parts. First, contaminant transport

through the grout, concrete vault, asphalt barrier, and unsaturated zone to the water table was evaluated using a two-dimensional model of the engineered disposal facility and the unsaturated zone. Second, contaminant transport through the aquifer is simulated on a pathline or advective-only basis. Pathlines are used to determine the areal influence of a plume emanating from the waste site, and to estimate the time required for contamination to move from the waste site to either a well located 100-m (328-ft) down-gradient of the Grout Disposal Facility or the Columbia River.

In analyzing the role of the unconfined aquifer in releases from the Grout Disposal Facility, pathlines starting from the trace of the disposal site on the water table were used to predict the flow paths and travel times to reach both a downgradient well used to irrigate a family farm and the Columbia River. Figure 3.3 illustrates the pathline trace from the waste site to a downgradient well. The pathlines were used to estimate the relative amounts of contaminated and uncontaminated groundwater drawn to a well, and to derive well intercept factors for concentrations of contaminants reaching the downgradient well.

Postulated natural and human-induced events that could disrupt near-surface disposal systems were studied as part of the HDWEIS (U.S. DOE 1987; Appendix R). Events considered for the variety of wastes and structures included in the HDWEIS are listed in Table 3.1 (from U.S. DOE 1987, Table R.1, pg. R.2). Of these events, only eight were considered to be of sufficient probability or consequence to

Figure 3.3. Flow Pathline of Contaminated Water to a Downgradient Well for an Irrigated Farm or Garden Scenario Where the Pumping Rate Influences the Flow Field

Table 3.1. Events Investigated for Potential Impact on Waste Disposal Systems

Irrigation	Glacial Flooding
Onsite	
Offsite	Other Surface Flooding
	100-Year Flood
Falling Objects	Standard Project Flood
Meteorites	Probable Maximum Flood
Airplane Crashes	Dam Failure
Space Debris	Rise in Sea Level
Drilling	Wind Erosion
Resource Exploration	Prevailing Winds
Water Well	Tomados
Excavation	Magmatic Activity
Major, Large Scale	Basalt Flows
Minor	Volcanism
	Igneous Intrusion
Resettlement/Farming/Gardening	Seismic Activity
Residential/Home Garden	
Post Drilling/Excavation Habitation	Criticality
Contaminated Water Supply Well	
Biotic Transport/Habitation	Diffusion
Climate State	
Current	Terrorism
Drier	
Wetter	Warfare

After U.S. DOE 1987, Table R.1, pg. R.2.

warrant analysis within the HDWEIS: climate, irrigation, impact crater (airplane crash), drilling intrusion, major excavation, residential/home garden, biotic transport, and post-drilling habitation. Clearly, some events represent their own transport pathway (e.g., falling objects that create significant impact craters), while other events define or influence the exposure pathway(s) (e.g., resettlement/farming/gardening). Irrigation, climate, and wind erosion could impact the unsaturated portion of the transport pathway by defining or altering the infiltration through the surface, and therefore, recharge to the aquifer. Deposition of surface soils (e.g., dune formation) could also influence infiltration and recharge. Finally, glacial-induced flooding will be considered because of evidence of its known influence on the unsaturated zone profile. The drilling, excavation, and resettlement/farming/gardening events will be discussed further in the exposure pathway section.

Irrigation and climate could influence the groundwater transport pathway in two ways: 1) by influencing the groundwater recharge rate away from the Grout Disposal Facility, changes in these events could result in a higher or lower water table and a corresponding thinner or thicker unsaturated sediment profile; and 2) by influencing the infiltration rate through the barrier system of the Grout Disposal Facility, either event could result in greater or lesser leaching of the wastes. Of these two potential impacts, the latter is anticipated to have the greater influence. The influence of a raised water table would be limited because the height of water table rise is limited by the natural surface and geologic features, such as the natural drainages to the north and east of the 200 Area plateau and Cold Creek valley to the southwest and natural internal drainage afforded by the highly conductive Hanford formation gravels beneath the 200 Area plateau in the vicinity of the Grout Disposal Facility.

Both erosion and deposition of soils occur on the Hanford Site because of wind. Although the rate of wind erosion is temporarily high during windstorms, the amount of fine-grained material removed is limited by the formation of lag concentrates from coarser material. This "armoring effect" is generally stable and tends to prevent further wind erosion unless the armored soil surface is disturbed. High winds in the Columbia Basin are associated with movement of weather fronts through the area and with thunderstorms. Tornadoes are infrequent and generally small in the northwest portion of the United States. Grazulis (1984) does not list any tornadoes for the region surrounding Hanford. A rate of 0.025 mm/yr was used for an estimated rate of wind erosion in the HDWEIS (U.S. DOE 1987). Assuming this rate were continued for 10,000 years, the land surface would be lowered by only 25 cm (10 in.). As noted in Section 2.7, the permanent isolation barrier has been designed to minimize erosion. A surface layer composed of gravel and silt loam soil will, when eroded by wind, present a gravel-armored surface that will resist further erosion. Therefore, wind erosion is not anticipated to have a major impact on the Grout Disposal Facility and was not included in the performance assessment.

The deposition of soils in the form of sand dunes does occur at Hanford. Stabilized and active dunes exist to the south and southeast of the Grout Disposal Facility (see Figure 2.10). Sand dunes are indicators of past, cumulative wind directions, and, therefore, the location of dunes to the south and downwind of the facility suggests that future dune formation over the facility is unlikely. Active dunes with the least, if any, vegetation lie furthest from the facility and adjacent to the Columbia River. Assuming that site decommissioning and closure activities in the 200 East and 200 West areas, which are upwind of the Grout Disposal Facility, do not create favorable conditions for dune formation, it is more probable that wind erosion events will dominate in the immediate vicinity of the Grout Disposal Facility.

While lesser forms of surface water flooding are not expected to influence wastes disposed on the 200 Area plateau, glacial-induced floods are known to have impacted the sediment profile of the disposal site. At the end of the last ice age, approximately 18,000 years ago, the retreat of glaciers caused cataclysmic flooding in the Pasco Basin. The Grout Disposal Facility is located near a high-energy flood channel on the south side of Gable Mountain. The Hanford formation is an example of the large-scale erosion and deposition that can occur. Thus, glacial flooding has been included as a transport pathway.

3.2.2.2 Exposure Pathways

Humans may receive radiation doses from radionuclides released from the Grout Disposal Facility into the environment through a variety of different transport and exposure pathways. Figure 3.4 (from Napier et al. 1988) illustrates the possible exposure pathways considered. These pathways are included in the GENII code, the code used to calculate radiation doses at the Hanford Site according to the International Commission on Radiological Protection (ICRP) 26/30 dosimetry model (ICRP 1975, 1977, 1979). The pathways included in GENII are general, and only those applicable to the exposure scenarios considered in this analysis were evaluated.

In the HDWEIS (U.S. DOE 1987, Appendix R), several plausible excavation events were postulated. The events included construction of highways or canals and basements in buildings. For excavation events, workers operating heavy machinery were assumed to be in a hole surrounded by contaminated soil. The workers in a hole would be directly exposed to radiation from radionuclides in the soil and suspended dust from the construction activities. Records and federal ownership of the land on which the Grout Disposal Facility is located would reduce the likelihood of major excavations. However, if records and controls have been lost or ignored, significant construction work and excavation activities could occur. The barrier and marker system planned for the Grout Disposal Facility is assumed to substantially reduce the probability of a major excavation; the excavators are assumed to be alerted to the danger by the markers internal to the barrier. Therefore, major excavations were not considered as an exposure scenario for the human intrusion pathway. Minor excavations or digging are assumed to be equivalent to drilling intrusion events because the amount of material removed and the processes of exposure would be similar.

As identified in Table 3.1 and Figure 3.4, biotic transport is another mechanism for transporting radionuclides from the Grout Disposal Facility to the environment. As reported in the HDWEIS (U.S. DOE 1987), transport of buried radioactive waste to the land surface by plants and animals is a slow process, but continued over long periods can result in substantial exposure of contaminants to humans from unprotected waste sites. At the Hanford Site, biotic transport has spread "nuisance" contamination (Cushing 1991). The 5-m (16.4-ft) depth of the grout and the presence of a riprap layer precludes intrusion of the grout vaults by animals and plant roots. Therefore, this pathway was not included for evaluation.

Drilling for either water wells or mineral exploration is a plausible mechanism for distributing contaminated soil on the ground surface. Monuments, barriers, and markers placed on and near the wastes may reduce the likelihood of intrusion by drilling, but they cannot preclude it. A single acute exposure to the individual doing the drilling, and a chronic exposure to post-drilling inhabitants of the site, were included as an intruder scenario.

The remaining pathways in Figure 3.4 were included in the performance evaluation of the Grout Disposal Facility. The conceptual model for environmental accumulation and exposure pathways is described later in Section 3.2.4.

S9211085.55

Figure 3.4. Available Exposure Pathways in the GENII Package

3.2.3 Conceptual Model of Environmental Transport Pathways

All releases from grouted wastes will be to the unsaturated sediments that surround the engineered vault and barrier system, with the exception of releases that occur as a result of catastrophic events, such as glacial flooding. Releases following catastrophic events will create their own release-transport-exposure sequence. With the exception of radon movement in the gas phase to the surface (described in Section 3.2.3.3), releases to the unsaturated zone rely on the liquid-phase in the soil profile (i.e., soil water) as the pathway for contaminant movement. Within the unsaturated soil environment, water can move upward, remain static, or move downward. If water moves upward (i.e., groundwater drawn to the land surface and evaporated), then the pressure profile from the water table to land surface would exhibit a pressure at the land surface sufficient to overcome the elevation head. It does not, and, therefore, it is known that soil water is either static or moving downward. If soil water is static (i.e., infiltration is negligible), then contaminants in the unsaturated zone can diffuse in all directions. Upward diffusion to the land surface or surface sediments would become a potential transport pathway. If infiltration occurs, then advection of contaminants dominates diffusion and contamination is swept downward to the aquifer and from there to groundwater wells or surface-water bodies that intercept the groundwater resource. Clearly, downward migration by infiltration and upward migration by diffusion are the primary pathways of interest.

3.2.3.1 Downward Migration

The grout waste management area covers approximately $9 \times 10^4 \text{ m}^2$ ($9.7 \times 10^5 \text{ ft}^2$) and the base of vault structures will be 60 to 70 m (200 to 230 ft) above the water table of the unconfined aquifer. The 33 vaults containing grouted waste will be paired and placed in rows as shown in Figure 3.5. Chapter 2 provides a detailed description of the location of the vaults and other grout facilities.

The analysis of downward-migrating contamination from 33 vaults is derived by developing the source term for the saturated zone groundwater model from analysis of an idealized two-dimensional vertical cross section (see Figure 3.2) that captures the symmetric half of a pair of vaults located in the vadose zone. In this case, a single vault is analyzed because each pair of vaults shares a single RCRA cover. Two primary assumptions of the conceptual model regarding the substitution of the two-dimensional cross section for the fully three-dimensional field setting are 1) the design and performance of each vault are similar in terms of its engineered systems and its underlying geohydrology, and 2) the flow of water and transport of contamination occur predominantly in the vertical direction through the vadose zone and into the unconfined aquifer underlying these vaults. These assumptions are based on our knowledge of the disposal facility and the natural environment in which the facility resides. Dominant processes in this analysis of an unsaturated sediment profile are water flow in unsaturated soils, and advection, diffusion, sorption, and decay.

Thus, contamination from the 33 vaults moves downward by convection and diffusion to the water table. While the vadose zone that underlies the Grout Disposal Facility is relatively deep, it is assumed the geologic structure or layering is not sufficiently pronounced to result in extensive lateral spreading of

Figure 3.5. Areal View of the Grout Treatment Facility Showing the Location of 44 Vaults as Forecast in 1990; Current Volume Estimates Would Yield 33 Units

contaminants (see Figure 3.2). Unlike the 200 West Area, which is underlain by the caliche layer, the 200 East Area lacks dominant layering (Lindberg et al. 1993, Appendix C; Rockhold, Fayer, and Heller 1993, Appendix J) that could result in extensive lateral spreading of contaminants introduced into the subsurface. Therefore, vertical movement of water and contamination is expected to dominate over any lateral spreading.

Linear scaleup of contaminant flux is used to convert the results from the analysis of a single vault to the field of 33 vaults and the total inventory. The fractional release obtained from the analysis of a unit inventory in a single vault is applied to the inventory for the entire vault field. This total contaminant flux is then spread evenly over the waste management area as leachate or contaminated recharge to the unconfined aquifer. This approach is described in greater detail in Section 3.5.4. This approach implies that all vaults fail simultaneously. While unlikely in an absolute sense, this approach is justified in light of the time frames of interest (e.g., thousands to tens of thousands of years) because failure of vaults and releases of contamination could occur over a relatively short period of time (e.g., several hundred years).

Contamination arriving at the water table is assumed to enter the aquifer underlying the waste management area as a uniform flux (Figure 3.6). In general, two-dimensional simulation of the vadose zone results in a distribution of point concentrations entering the aquifer. Use of a uniform flux is a necessary

Figure 3.6. Three-Dimensional Schematic Showing the Vertical Projection of the Grout Vaults Onto the Water Table of the Unconfined Aquifer

simplification resulting from the scale-up process. This treatment involves the fractional release (an integrated flux) from the base of the two-dimensional cross-section and the land surface area associated with all of the vaults, assuming that lateral spreading or dispersion of contamination in the vadose zone is no greater than the surface area of the waste management area. This assumption incorporates a degree of lateral spreading or dispersion in the estimate of contaminant concentration leaving the unsaturated zone. It also implies that the development of preferential flow and transport paths from individual vaults to the water table is improbable. Clastic dikes have been identified within the Grout Disposal Facility; however, they are not believed to be continuous to the water table. If they are found to extend to the aquifer, they could represent a preferential flow path. If present, preferential pathways for individual vaults would result in different estimates of flux (e.g., earlier) and point concentrations (e.g., higher) leaving the unsaturated zone and entering the aquifer; however, the effect on overall release from all vaults is assumed to be small.

Once contamination has entered the unconfined aquifer, it moves with the groundwater until the groundwater is intercepted by a well or discharges to a spring, pond, lake, or river. Just as the Grout Disposal Facility represents the origin of the contaminant plume, the point of interception or discharge represents the end of the groundwater pathway. As will be described in the following section on exposure scenarios, a groundwater well located only 100-m (328-ft) downgradient of the facility is a defined point of interception. Similarly, exposures to contamination in Columbia River water define another pathway of interest.

In order to produce simulations of the aquifer that represent future groundwater flow patterns, a model of the unconfined aquifer was calibrated using a suite of boundary conditions (river stage, known discharges, etc.) and records of groundwater elevation. Removal of site discharges from the model produced a post-Hanford aquifer model. In general, discharges from Cold Creek and Dry Creek valleys flow across the Hanford Site and into the Columbia River. Removal of site discharges will eliminate groundwater mounds and create a more predictable aquifer in the vicinity of the Grout Disposal Facility. However, this remains a complex region of the aquifer because of its proximity 1) to basalt outcrops above the water table and land surface (i.e., Gable Mountain), 2) to erosional windows to the underlying confined aquifers, and 3) to regions of the complete erosion of the Ringold formation.

Previous simulations of the unsaturated zone-unconfined aquifer transport pathway (U.S. DOE 1987 pg. Q.2-Q.4) have shown the time of travel within the unsaturated zone is much greater than that in the aquifer. For example, existing contaminant plumes originating in the 200 East Area have reached the Columbia River in 25 to 30 years. This relatively minor role of the aquifer segment in the transport pathway has resulted in the use of a pathline tracer methodology to estimate the time of arrival of contaminant at the groundwater well or river. The quality of groundwater recovered from the aquifer by the well has been approximated by using a well intercept factor based on the quantities of clean and contaminated groundwater recovered.

3.2.3.2 Upward Migration - Soil Water

The upward migration pathway is conceptually similar to the downward pathway except the boundary condition at the upper surface of the unsaturated zone profile is changed. The downward pathway is created by assigning a downward-directed infiltration rate to the surface. A diffusion-dominated upward transport pathway is created by setting the infiltration to zero. From the hydraulics viewpoint, this treatment does not produce any downward or upward movement of water through the boundary. From the transport viewpoint, it eliminates advective transport through the boundary and into the atmosphere. The transport problem boundary can be assigned a zero-gradient condition, thus also eliminating diffusive transport through the boundary. This conceptual model of diffusion within the backfill soil will cause contamination to be stored in the surface sediments and then to diffuse downward after the source is depleted.

3.2.3.3 Upward Migration - Gas Phase

The migration of radon gas from the waste to the surface was simulated using a conservative model of the vault and barrier system. In concept, the radon generated within the grout must escape from the grout and move through the concrete vault, asphalt barrier, and RCRA cover before being released through the isolation barrier to the surface. Conservative values were adopted for grout and barrier diffusivity, radium-226 source, and the thickness of the overlying barrier system.

3.2.3.4 Water-Vapor Diffusion

Water-vapor diffusion does not create a new transport pathway, but it may affect the previously described downward-migration pathway by supplying a greater amount of water to the waste form or disposal system surface. Because of the high salt content of the wastes, a water vapor density gradient will develop between the waste and its surrounding soil environment. Water vapor will diffuse from the soil to the waste in response to the reduced water vapor density in the grout. This water vapor should condense on the outer surface of the concrete vault and could leach contamination that has either advected or diffused to the exterior vault surface. The quantity of water that could be drawn to the waste by this phenomena has been estimated and will be superimposed on some of the downward-migration pathway simulations to demonstrate the potential influence of water vapor diffusion.

3.2.4 Conceptual Model of Environmental Accumulation and Exposure Scenarios

This section describes the scenarios used to evaluate the impact of human exposure to radionuclides and other hazardous chemicals potentially released from the Grout Disposal Facility. The scenarios for human exposure generally fall into four categories: 1) direct human intrusion into the disposal site; 2) transport of hazardous materials to groundwater and subsequent use of the groundwater by humans; 3) transport of contaminated groundwater to the Columbia River, which is used by downstream populations for a variety of activities; and 4) direct contamination of surface soil by upward diffusion or as a

result of disruption of the disposal site by natural events such as glacial-induced flooding. The assumptions used for the groundwater and river scenarios and the intruder scenarios are described here. The scenarios considered in this document are based on those used for evaluating various alternatives for disposal of Hanford defense wastes, including grout (U.S. DOE 1987, Appendix R), but have been updated to include more recent information on exposure parameters.

The scenario descriptions in this section are general. Appendix M presents detailed explanations of the exposure scenarios and the sources for parameters used in the dose calculations. The analysis was conducted for a time period appropriate to each scenario, but in all cases it was carried to a future time sufficient to determine the maximum dose to a member of the public.

3.2.4.1 Groundwater Scenarios

Use of groundwater contaminated by radionuclides from the Grout Disposal Facility is the basis for human exposure in the groundwater scenarios. The impact on a particular individual in these scenarios depends primarily on how the groundwater is used. Potential exposure pathways include direct consumption of water through drinking and cooking, use of groundwater to irrigate terrestrial food products for human consumption, and use of groundwater to provide water for livestock or to irrigate feed crops consumed by animals whose products are subsequently eaten by humans. Application of groundwater to the soil surface during irrigation may also result in direct exposure to radiation from radionuclides accumulated on the ground, or to inhalation of radionuclides resuspended from the contaminated soil surface. Three groundwater use scenarios were addressed in this study.

Individual Drinking-Water Scenario. The simplest groundwater scenario consists of a case in which the water is used only for domestic purposes, but not for production of food crops. This scenario assumes that an individual consumes 2 L/d (0.53 gal/d) of contaminated water but has no other potential routes for internal or external exposure. It provides the basis for comparison to the radionuclide dose standards in DOE Order 5820.2A and the primary and secondary drinking-water regulations, as discussed in Chapter 1. This scenario is included for evaluation of the groundwater protection objective.

Irrigated Farm Scenario. This scenario is based on groundwater used not only for domestic purposes, but also for irrigation of crops on a farm that produces a fraction of the individual's terrestrial foods (vegetables and fruits) and animal products (meat, milk, and eggs). It also assumes that the individual is exposed to external radiation from the soil surface and to radionuclides in resuspended soil through inhalation. The drinking-water consumption rate used in this scenario is a population average, which is somewhat more realistic than the 2 L/d used for regulatory purposes. In this scenario, the size of the irrigated area used for growing human and animal food crops, 20,000 m² (~5 acres), requires pumping irrigation water at the rate of 45 m³/d, ($\sim 1.2 \times 10^4$ gal/d), a rate that captures a portion of the contaminated plume from the Grout Disposal Facility plus some uncontaminated water from the aquifer. The concentration of radionuclides in irrigation water for this scenario is therefore somewhat lower than that modeled

for the contaminated-groundwater plume. This scenario provides the basis for comparison to the radionuclide dose standards for all pathways in DOE Order 5820.2A. The dose limit for all pathways was defined in Chapter 1.

Individual Irrigated Garden Scenario. This scenario is based on use of groundwater for domestic use and irrigation of crops that produce a fraction of the individual's terrestrial foods. The major difference between this scenario and the irrigated farm scenario is the omission of ingestion exposure pathways for animal products. All other exposure pathways and parameters for this scenario are identical to those for the irrigated farm scenario. Because of the smaller volume of water required for irrigation in this scenario, it was assumed that groundwater withdrawn for domestic and irrigation purposes would be obtained entirely from the contaminated plume downgradient from the Grout Disposal Facility through a low-volume well. Although the irrigated farm scenario has historically resulted in the highest individual dose estimates for shallow land burial of radioactive materials (U.S. DOE 1987), this scenario was evaluated because the increased groundwater concentration might result in a higher dose to the maximally exposed individual, even without the animal product consumption pathways. The doses estimated for this scenario were also compared with the radionuclide dose standards for all pathways in DOE Order 5820.2A.

Community Well Scenario. The collective dose was estimated based on the irrigated garden dose to an individual as described for the general public protection objective. The peak dose in the individual irrigated garden scenario was multiplied by 80 to obtain an estimate of the potential collective dose resulting from the use of groundwater. The volume of contaminated groundwater in the plume at 100-m (328-ft) downgradient from the disposal site is sufficient to meet domestic needs and to produce a portion of fruits and vegetables consumed by a population of 80 individuals. Use of groundwater to supply the domestic needs of a larger population would result in substantial dilution of contaminated groundwater by clean water from the aquifer. Therefore, use of the minimum population size represents the maximum collective dose in this scenario.

3.2.4.2 Catastrophic Flood Scenario

The catastrophic flood scenario considers the potential effect of natural forces on the Grout Disposal Facility, based on evidence for similar flooding at the end of past ice ages. In such an event, the entire Pasco Basin could be flooded and the existing sedimentary deposits would be disrupted to a considerable depth. The scenario evaluated for this analysis presumes that the entire radionuclide inventory of the grouted waste is exhumed by such a flood 50,000 years after disposal. The radionuclides are then uniformly distributed over an area equivalent to that of the Hanford Site [1.450 km^2 (560 mi^2)] at a depth of 10 m (33 ft). The exposure pathways included in this scenario are the same as those considered for the irrigated farm scenario, except that the drinking-water source is assumed to be uncontaminated. In this case, radionuclides are deposited directly in the surface soil, as opposed to the irrigation scenario where groundwater provides the source of radioactive materials. The dose to an individual for this scenario is compared with the all-pathways performance objective for protection of the general public.

3.2.4.3 Upward Diffusion Scenario

This scenario is equivalent to the glacial flood scenario in that it involves direct contamination of soil rather than secondary contamination following transport of radionuclides to groundwater. In this case, the radionuclides are assumed to diffuse upward from the buried vaults to the surface soil in the absence of net groundwater recharge from precipitation. As with the flood scenario, all pathways are considered except drinking water, and the results are evaluated by comparison with the all-pathways performance objective for protection of the general public.

3.2.4.4 River Scenario

This scenario was developed to evaluate the collective dose to a population of 5 million people assumed to live on or near the Columbia River downstream from the Hanford Site in the future. Radionuclides in groundwater beneath the Hanford Site ultimately enter the Columbia River in the Hanford Reach and are then transported downstream by the river (Woodruff, Hanf, and Lundgren 1992). The river is used as a source of drinking and irrigation water, as in the groundwater irrigated farm scenario. In addition, the river is a source of aquatic food (fish) and is used for a variety of recreational purposes such as swimming, boating, and other shoreline activities.

The pathways considered in this scenario include use of contaminated irrigation water to produce all terrestrial and animal foods for the population and use of the river for drinking water. The consumption of contaminated fish is based on the total quantity of panfish caught in the immediate vicinity downstream from Hanford. The population is exposed to external radiation from radionuclides in the river and sediments through recreational activities, and to radionuclides in soil contaminated by irrigation. Inhalation of resuspended contaminated soil is also included. The food consumption rates used for this scenario are population averages, which are somewhat lower than those used for the maximum individual dose calculations in the groundwater scenarios.

For the purposes of this scenario, the quantity of radionuclides entering the river annually through groundwater was assumed to be diluted by a volume of water corresponding to the annual average river flow rate at Hanford (Woodruff, Hanf, and Lundgren 1992). The calculations are based on the assumption that only contaminated river water was used for consumption and irrigation. In reality, a large fraction of the water used for these purposes downstream from Hanford comes from uncontaminated sources. Columbia River flow is also substantially diluted by inflow from tributaries immediately downstream, e.g., the Yakima and Snake rivers.

Collective doses are not regulated by state or federal agencies, therefore no standards for radiation doses to populations are available by which to evaluate the potential exposures. A relative measure of the impact of collective radiation exposure can be obtained from the number of excess fatal cancers resulting from radiation exposure to a given population. The current value recommended by international radiation protection organizations for risk from radiation exposure to the general population is approximately 500 fatal cancers per million person-rem (ICRP 1991).

3.2.4.5 Intruder Pathways and Scenarios

Intrusion directly into the Grout Disposal Facility becomes a possibility after active institutional control of the Hanford Site by the federal government ends. DOE Order 5820.2A (U.S. DOE 1988a) provides for a maximum institutional control period of 100 years, after which only passive mechanisms such as markers, monuments, and public records are available to alert intruders to the presence of hazardous waste. DOE-RL 5820.2A (Hanford Site implementation of the DOE Order, U.S. DOE 1990a) requires the use of barriers and markers sufficient to deter intruders for 500 years at disposal sites where waste remains hazardous beyond the 100-year institutional control period. That provision is also consistent with U.S. Nuclear Regulatory Commission (NRC) 10 CFR 61 requirements for disposal of commercial low-level radioactive waste. Although barriers are likely to be successful, intruder scenarios were evaluated at 100, 300, 500, and 1,000 years after disposal.

Drilling Scenario. Drilling for water or mineral exploration is a potential mechanism for bringing radionuclides disposed in a grout waste form back to the surface where they would be accessible for human exposure. The presence of engineered barriers and markers as described in Chapter 2 provides a deterrent to drilling through the disposal site, but these warning systems cannot entirely preclude the possibility. The drilling scenario considers exposure to an individual involved directly in drilling a well or borehole through a grout disposal vault. Radioactive material from the drilling core is assumed to be transported to the surface and spread over a relatively small area. During the drilling operation, the operator is exposed by inhaling radionuclides suspended in the air. While completing the well and disassembling the drilling equipment, the operator also receives external exposure from radionuclides that have been spread over the ground surface. Radionuclide concentrations on the ground surface are based on the radionuclide concentrations in the waste feed stream rather than the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with adding dry materials to form the grout.

Post-Drilling Home Garden Scenario. The post-drilling home garden scenario was used to evaluate the dose to an individual who inhabits the disposal site after radioactive material from the drilling core is brought to the surface. In the process of grading the site and constructing a residence, the radionuclides are assumed to be spread over a larger area and mixed with the uncontaminated surface soil to a depth of 15 cm. Exposure pathways in this scenario include ingestion of fruits and vegetables grown in the contaminated soil, inhalation of resuspended radioactive materials, and external exposure to penetrating radiation from radionuclides in the surface soil. Radionuclide concentrations mixed into the 15-cm-thick contaminated surface layer are based on radionuclide concentrations in the waste feed stream rather than in the grout. This approach is conservative by 30% to 40% with respect to the average concentration in grouted waste because of the volume increase of 30% to 40% associated with the addition of dry materials to form the grout.

3.2.4.6 Evaluation of Hazardous Chemicals Released from Grout

The transport of hazardous chemicals other than radionuclides that may be released from grouted waste was included in this analysis. These results are included for information only because hazardous chemicals are regulated under the RCRA permit for the disposal site. The concentrations of these chemicals in well water or groundwater as compared to the federal EPA primary and secondary drinking-water standards [40 CFR 141, 56(138) FR 33050, 57(138) FR 31776] were used as the benchmark for the relative hazard presented by the materials. Primary drinking-water regulations are based in part on the risk of carcinogenic and noncarcinogenic health effects from chemicals ingested by human populations, and therefore provide an index against which the groundwater concentrations of these materials can be evaluated. Secondary drinking-water regulations are intended to control contaminants that primarily affect the aesthetic quality of the water. However, at considerably higher concentrations these chemicals may have health implications.

Drinking-water regulations may not be applicable to well scenarios involving relatively low pumping rates and doses to an individual for which comparisons are made. Limits for some contaminants apply only to community water systems having at least 15 connections used by year-round residents or that serve at least 25 year-round residents. Limits for other contaminants are more broadly applicable. However, the regulations are used as a point of comparison to evaluate degradation of water quality.

3.2.5 Flow and Transport Models

Conceptual models of release and transport described in the preceding sections have referred to a number of water flow and transport processes relevant to the unsaturated zone or unconfined aquifer or both. Before presenting data and model parameters specific to the grouted waste, the engineered disposal system, and the natural environment, these processes need to be described and related to model parameters. These processes fall into two categories: water flow and contaminant transport. Process models adopted for simulations are based on porous media and equivalent porous media concepts, i.e., the subsurface is composed of a matrix of solid particles (e.g., sand, silt, clay, gravel, etc.) and a network of voids. Thus, other approaches to modeling discrete fractures in degraded engineered structures are not discussed. The primary purpose of this section is to define terminology. Those readers familiar with process models and parameters used in the porous media model can go to the description of the source term and engineered system in Section 3.3.

3.2.5.1 Water Flow

Brief descriptions of water flow in saturated and unsaturated media are followed by a discussion of water vapor flow as it relates to the high salt content of these grouted wastes. A similarly brief presentation is made using equations of water flow in Appendix P, Section P.1.1.

Saturated Water Flow. Water flow through a saturated porous media is governed by the empirical relationship known as Darcy's Law (Freeze and Cherry 1979, pg. 15-36) and the equation describing conservation of mass. Water flows from areas of high potential (or energy) to areas of low potential (e.g., from areas of recharge at high elevation, to areas of discharge at low elevation). The flow rate of water is proportional to the hydraulic gradient (the variation in potential in the direction of flow) and the cross-sectional area. The proportionality constant is known as the saturated hydraulic conductivity, K_s . Multi-dimensional models employ a tensor form of K_s , denoted K_{ij} , where the subscripts represent the x, y, and z spatial dimensions and K_{ij} is a 3 x 3 matrix. The principal components of the tensor, the diagonal entries, are often denoted K_x , K_y , and K_z when the axes of the conductivity tensor align with the coordinate axes and the off-diagonal entries to the tensor are then zero.

Darcy's Law defines the discharge of water through a cross section of porous media. However, in contaminant transport problems it is of interest to determine the average velocity of water flowing through the media. This is because neutral contaminants, those that do not sorb, move with the water. The average velocity of the pore water is determined by dividing the flow rate of water by the total porosity (θ_T) or effective porosity (θ_E) of the media (Freeze and Cherry 1979, pg. 36-38, 70-71, 388-389). Porosity is the ratio of void space to total volume. Effective porosity is a somewhat lower estimate of porosity acknowledging that some pore and void space does not contribute to flow.

Unsaturated Water Flow. The feature of the unsaturated zone that distinguishes it from the saturated zone is the degree of water saturation in the pore space. In the saturated zone all pores are filled with water; in the unsaturated zone they are not. Water still flows from regions of high potential to regions of low potential, but capillary forces now influence the conductivity of the porous media. While the flow rate of water is proportional to the gradient in total potential, the proportionality is not constant. (For an explanation of potential, see Appendix P.) The hydraulic conductivity of unsaturated media is a function of the degree of saturation, $K(\theta)$ (where saturation is equivalent to moisture content, θ), or the pressure head, $K(\psi)$. Soil moisture content is also a function of pressure head, i.e., $\theta = \theta(\psi)$. $K(\psi)$ is the relative permeability curve, and $\theta(\psi)$ is the water retention characteristic. These two relationships are characteristic curves of an unsaturated media. Figures 3.7 and 3.8 are examples of characteristic curves. The classical equation used to describe transient unsaturated flow is referred to as Richards' equation after the soil physicist who first developed it (Richards 1931).

Simulating transient water flow in unsaturated media also requires a knowledge of specific capacity, $C(\psi)$. This parameter describes the change in the water-storing capacity of a porous media as a function of pressure head. Analytically it is the slope of the water retention characteristic curve (i.e., $C(\psi) = d\theta/d\psi$); thus once $\theta(\psi)$ is known, the specific capacity is known. Occasionally, to simplify simulations the specific capacity is assigned a constant value.

S9211085.46

Figure 3.7. Example of Water Retention Characteristics (after Hillel 1982)

S9211085.47

Figure 3.8. Example of Unsaturated Hydraulic Conductivity Relationship (after Hillel 1982)

As in the case of saturated flow, the average velocity of water in the unsaturated media is of interest for the contaminant transport problem. Soil moisture content defines both the volume of water and the cross section of water in the unsaturated media. Therefore, average water velocity is determined by dividing the flow rate of water (as defined by Richards' equation) by the moisture content. As soils or sediments approach full saturation, moisture content approaches total porosity.

Use of characteristic curves in numerical models generally requires that laboratory or field data be described by analytical models. This technique promotes efficiency in numerical solutions because values can be determined exactly, thus avoiding interpolation between data points in a table and assuring continuous derivatives necessary for evaluating the specific capacitance. A number of methods have been developed to describe characteristic curves. The relationship selected for use in this performance assessment is a closed-form analytical model for representing the water retention characteristics and unsaturated hydraulic conductivity function, published by van Genuchten (1978). Specifically, for the moisture content, θ , expressed on a volumetric basis:

$$\theta = (\theta_s - \theta_r) \left[\frac{1}{1 + (\alpha\psi)^n} \right]^m + \theta_r \quad (3.1)$$

where θ = volumetric moisture content (dimensionless)

θ_s = saturated moisture content (dimensionless)

θ_r = residual moisture content (dimensionless)

α = fitting parameter (L^{-1}) approximately equal to the inverse of the air entry potential of the soil

ψ = the matric potential or capillary pressure head of water (L)

$m = (1 - 1/n)$

n = fitting parameter (dimensionless).

The relative hydraulic conductivity under unsaturated conditions is expressed in the form proposed by Mualem (1976) and restated by van Genuchten (1978). Relative hydraulic conductivity is expressed as follows:

$$K_{rw} = \frac{K}{K_s} = \frac{(1 - (\alpha\psi)^{n-1} [1 + (\alpha\psi)^n]^{-m})^2}{[1 + (\alpha\psi)^n]^{m/2}}$$

where K_{rw} = relative hydraulic conductivity (dimensionless)

K = unsaturated hydraulic conductivity (L/T)

K_s = saturated hydraulic conductivity (L/T)

and α , ψ , m and n are as defined above.

This model and soil hydraulic data for the engineered and natural materials are presented in Appendix J.

Water Vapor Diffusion. The high salt content within the pore fluid of the grout produces a depression in the water vapor pressure over the grout. The salt content in the surrounding soils is relatively low, so the vapor pressure of moisture in the soils surrounding the vault is higher than the vapor pressure of water over the grout. This condition creates a concentration gradient in the mass concentration of water vapor in the gas phase, providing the driving force for diffusion of water vapor from the soil to the grout. The movement of water vapor within soils is discussed by Hanks and Ashcroft (1980). The phenomenon of water vapor diffusion to a high salt content waste has been described by Cary, Gee and Whyatt (1991). The diffusion of the water vapor in the gas phase can be described by Fickian diffusion in one dimension as follows:

$$\dot{m} = -D_v \left(\frac{dc}{dx} \right) A \quad (3.3)$$

where $\dot{m}$ = mass rate of water vapor diffusion (M/T)

D_v = effective vapor diffusion coefficient (L²/T)

C = water vapor mass concentration in gas phase (M/L³)

$\frac{dc}{dx}$ = water vapor mass concentration gradient (M/L⁴)

dx

X = spatial coordinate (L)

A = cross-sectional area (L²)

3.2.5.2 Contaminant Transport

Brief descriptions of transport phenomena in porous media are used to introduce the process model parameters, which are described in subsequent sections. See Appendix P, Section P.1.2, for a similar presentation that introduces the basic equations of transport processes.

Diffusion. Diffusion is the process whereby ionic and molecular constituents move in the direction opposite their concentration gradient (i.e., from high to low concentration). Diffusion acts whenever concentration gradients are present, but is important only in situations where diffusive flux is comparable to or greater than advective flux. As described by Fick's first law (Freeze and Cherry 1979, pg. 103), the

mass of a diffusing contaminant through a given cross section per unit time is proportional to the negative of the concentration gradient. The proportionality constant is known as the diffusion coefficient, D . Diffusion coefficients are often determined in the laboratory and reported as diffusion coefficients in water. Care has been taken in this study to define effective diffusion coefficients for the transporting medium (e.g., soil water, bulk soil, asphalt).

The effective diffusion coefficient for soils and sediments is a function of moisture content, and an empirical relationship by Kemper and van Schaik (1966) was used to calculate parameter values for the various natural media in this study. The formula used to calculate effective diffusion coefficients as a function of moisture content was

$$D_e(\theta) = D_{ab}(a)(e^{b\theta}) \quad (3.4)$$

where $D_e(\theta)$ is the effective diffusion coefficient of an ionic species in the particular soil or sediments, D_{ab} is the effective diffusion coefficient of the same species in water, and a, b are empirical constants. This correction for the effect of moisture content was applied to natural media and the RCRA cover material, but not to the gravel or engineered materials in the disposal system.

Dispersion. The concentration of individual solutes within components of the engineered system, soil, and groundwater will be affected by the process of dispersion. Dispersion, also referred to as mechanical dispersion, is the process resulting from mechanical mixing of solutes during their transport by advection (Freeze and Cherry 1979). This process creates a tendency for solutes to mix and spread out from the path they would be expected to follow under the average hydraulics of the flow system. The mixing occurs as contaminants follow different flow paths through the porous media. The contaminants are transported through a portion of the porous media pore space that actively participates in flow, termed the effective porosity. Mechanical dispersion is the process used to describe variations in contaminant concentration resulting from velocities higher and lower than the average, and paths more or less tortuous than the average. The resulting early arrivals, persistent long-term low concentrations, and lateral or transverse spreading are all accounted for by mechanical dispersion. The net effect of dispersion causes dilution of solutes as the solutes are transported along flow paths. When combined with diffusion, this spreading, mixing, and dilution process is referred to as hydrodynamic dispersion.

While not included explicitly in the simulation of contaminant transport within the unsaturated zone, dispersive phenomena are included implicitly by the method used to introduce contamination to the aquifer. That is, the fractional release predicted for a single vault is applied to the total inventory for the entire vault field, and this total contaminant flux is uniformly applied over the waste management area as contaminated recharge to the unconfined aquifer. Thus, wastes disposed to 33 individual vaults are assumed to disperse laterally in the unsaturated zone and contaminate all recharge entering the aquifer from the waste management area. Initially this assumption may appear to be completely arbitrary;

however, viewed in the context of the groundwater contamination problem it is a reasonable approach. The waste management area boundary extends only to the outermost wall of the outermost vaults (see Figure 3.5). Thus, lateral dispersion is underestimated because perfectly vertical infiltration through 60 to 70 m (200 to 230 ft) of unsaturated zone is not possible. Longitudinal dispersion, which would lead to somewhat earlier arrival times but lower peak flux and concentration predictions, has been neglected. The very long-term nature of the release and consequence analysis, and the reliance on predictions of peak or maximum concentration, justify the approach taken. Whether a peak occurs after 9,000 or 9,100 years is not as significant as the estimated peak level of groundwater contamination.

As described in the section on the downward subsurface migration pathway (Section 3.2.3.1), the travel time in the aquifer is short (on the order of days) in comparison to travel time in the unsaturated zone (on the order of thousands of years). This relatively short travel path, when associated with the long-term release from grouted wastes, makes consideration of longitudinal or lateral dispersion in the aquifer unnecessary. Once established, the contaminant plume in the aquifer will have such a long-term presence that dispersion in the aquifer will not reduce maximum concentrations a short 100 m away from the site. Similarly, the maximum contaminant flux entering the Columbia River will occur over a sufficiently long period of time to minimizing any impact from dispersion within the aquifer.

Sorption. The transport of some contaminants is affected by adsorption onto the porous media or precipitation in minerals. A linear sorption isotherm model is commonly used to simulate these processes in the subsurface environment. This model partitions the contaminant between the liquid and solid phases in the porous media by fixing the ratio of mass sorbed per unit mass of dry solids to concentration in solution (Freeze and Cherry 1979, pg. 402-408). This ratio is known as the distribution coefficient, R_d , and, through manipulation of the transport equation results in a retardation factor, R . A R_d of zero produces a R of 1, which implies contaminants that do not sorb ($R_d = 0$) move with the velocity of the water. When the R is two ($R = 2$), the associated contamination moves at one-half the velocity of the water. As the R_d increases, the R increases, and the contaminant moves at a decreasing velocity. In general, this model is valid if the reactions that cause partitioning are fast and reversible and if the R_d is independent of the contaminant concentration in solution.

The R_d is affected by both the surface chemistry properties of sediment minerals as well as the solution chemistry of the pore fluids. Vadose zone sediments do not exhibit much variation beyond pH or cation exchange capacity (Ames and Serne 1991), which are functions of mineral surface properties. Pore fluid chemistry (e.g., pH, Eh, and dissolved solids) in porous materials is controlled by mineral-fluid reactions and is generally dominated by the minerals present, particularly for systems with high solid-to-liquid ratios. The empirically determined R_d as described above for both sediments and grout incorporate these surface chemistry and fluid chemistry effects as a combination of all possible sorption mechanisms, but it is difficult to evaluate individual mechanisms separately. Also, both vadose zone and groundwater pathways are inhomogeneous, which can cause some variation in sorption properties with distance. For these reasons, as well as the lack of site-specific geochemical data, it is generally accepted that a linear sorption isotherm model based on a range of empirically determined values from Hanford sediments and

grout is satisfactory for performance assessment calculations if sufficient conservatism is included (Ames and Seme 1991). Separate distribution coefficients were used for the grout and sediments, but values were constant in each region of the model domain.

Because of the impracticality of modeling each contaminant separately with a contaminant-specific R , as well as the lack of site-specific data on a wide range of possible contaminant-sediment systems, individual contaminants have been grouped into transport groupings based on the lowest observed value for all contaminants in a particular group. Also, a conservative estimate of contaminant mobility is made by calculating retardation factors based on both conservative R_d values and assuming saturated porosity. It is not expected that properties such as bulk density and porosity in sediments will change significantly with time, so the values are considered to remain constant for this assessment.

Decay. Radionuclides decay (NCRP 1984) with time, reducing the concentrations; e.g.,

$$\frac{N}{N_0} = e^{-\lambda t} \quad (3.5)$$

where N/N_0 = fraction remaining

N = concentration at time = t

N_0 = initial concentration

λ = $\text{Ln}(2)/(\text{half life})$

t = time.

The half life (yr) of each radionuclide is given in Table 2.4.

3.3 Source Term and Engineered System

The Grout Disposal Facility, including the grout, concrete vault, asphalt barrier, and RCRA and protective barriers, is designed to contain and control the release of radionuclides into the environment. Describing the long-term performance of the engineered disposal system defines the source term for this performance assessment. The description of the source term includes a discussion of the radionuclide and chemical inventories planned for disposal, and the description of the engineered system includes a conceptual model of the Grout Disposal Facility. The conceptual model describes the behavior of the engineered system while the system is intact and as it degrades, including mechanisms for degradation of

system components and contaminant release and transport from the disposal facility. This information supports the brief conceptual descriptions of release and transport that have already been presented.

Contaminants are in the grout as precipitated solids, adsorption products, hydration products, and aqueous species. Contaminants bound in the solid matrix are released to pore fluids in the grout by dissolution and desorption. Contaminants in the pore fluids move by diffusion and advection. Diffusion is the dominant mechanism for release when the engineered barrier system is intact (i.e., primarily while the asphalt barrier acts as a hydraulic barrier). When the asphalt barrier and concrete vault degrade, moisture from recharge and water vapor return can enter the grout and pore water from the grout can drain into the surrounding soil, carrying contaminants out of the Grout Disposal Facility by advection. Several processes control the release of radionuclides from grout and the facility. The performance of the source depends on performance of the engineered system, so the effects of degradation and failure of the engineered barriers are addressed in this section of the performance assessment. Available data will be presented and discussed for release and transport process models applicable to the waste form and engineered system. Model parameters associated with degraded states of the engineered vault and barrier system will be presented and justified to the extent possible. In many cases justification cannot be rigorous because of the long-term nature of the degradation and the absence of relevant engineering, hydraulic, or transport data for degraded materials. In several instances, conservative selections have been made in either the timing or severity of degradation, or both.

3.3.1 Radionuclide and Chemical Inventories

As described in Chapter 2 and Appendix E, 122 million liters of waste are currently identified for disposal as grout in 33 vaults. The radionuclide inventory for the waste is provided in Table 2.4. Table 2.4 includes the decay half lives used in the analyses. The volume of waste represents a sum of existing concentrated wastes, future concentrated wastes, and low-level waste streams from the treatment of neutralized current acid waste (NCAW), neutralized cladding removal waste (NCRW), Plutonium Finishing Plant (PFP) waste, and complexed concentrate (CC) waste. Three approaches were taken to prepare inventory estimates. Concentrations in existing concentrated wastes were estimated using weighted averages for measured constituent concentrations or were based on correlation factors for constituents not analyzed. Concentrations from evaporator-derived wastes were estimated based on source concentration and the volume reduction factor of the evaporator. Operations records were used to determine the transfer history of waste volumes and hence concentrations. The most current material balance forecasts were used to estimate the character of low-level waste streams to be generated by future pretreatment. Methods used to estimate the inventory, and special methods used to estimate the inventory of some key radionuclides, are described in Appendix E.

All of the radionuclides listed in Table 2.4 were analyzed for the irrigated farm scenario in the central sensitivity case (to be described in Sections 3.6.1 and 3.6.5.1). The ingrowth of daughter products is discussed in Appendix P (Section P.2.1). The analysis revealed that radionuclides present in low concentrations or with short half lives or both could be omitted from the long-term dose calculation. Similarly, radionuclides that were highly sorbed in the grout waste form and to sediments of the unsaturated zone

were shown to have negligible impact on the long-term dose estimate. Therefore, the following radionuclides were not included in other calculations of long-term dose: niobium-94 and -95; zirconium-95; cerium/praseodymium-144; europium-152, -154, and -155; thorium-230; plutonium-238, -239/240, -241, and -242; americium-241; and curium-243 and -244. All intruder dose calculations included the entire radionuclide inventory as listed in Table 2.4.

Total feed concentrations for chemicals in molarity (mol/L) and their molecular weights also are provided in Table 2.4. Chemicals have been included in this radiological performance assessment for information only. Only those chemicals listed in the primary and secondary drinking-water standards have been analyzed and presented in Chapter 4.

3.3.2 Conceptual Description of the Long-Term Performance of the Engineered Disposal System

During the first 100 years, the grout and engineered disposal system are expected to function as designed. All major components will remain intact. Degradation during this period will be limited to surface biodegradation of the asphalt barrier at the soil-asphalt interface and cracking of the grout/concrete sealing the roof plant joints (Figure 3.9). Despite this minor cracking, the overall system will retain its high integrity. Movement of the waste will be limited to diffusion within the components of the disposal system. The asphalt barrier will retain its integrity, so water will not infiltrate the grout.

By about 1,000 years, degradation will have a minor but recognizable effect on the integrity of the engineered disposal system. Horizontal and vertical cracks will appear in the upper corners of the asphalt barrier. These cracks are caused by the disintegration of the thermal insulation board and slumping of the asphalt barrier walls (Figure 3.10). The cracks will be the first through-wall cracks in the asphalt barrier, and they will provide an avenue for water to enter and contaminants to leave the concrete vault. Biodegradation will continue on the exterior surface and begin on the interior and crack surfaces of the asphalt barrier. The reinforced concrete vault will show additional cracking. Through-wall cracks are expected at construction joints because of the corrosion of steel water stops placed after a concrete pour to ensure a good seal between one pour and the next. Surface cracks on all concrete surfaces are expected because of rebar corrosion. Cracking at the roof plant joints will continue. Seismic events and the transfer of external loads from the vault to the grout monolith will cause some fracturing of the grout itself.

These degradation processes will continue for tens to hundreds of thousands of years. Cracking of the concrete and grout will continue because of corrosion and seismic events. Biodegradation of the asphalt barrier surfaces will continue. Eventually, additional through-wall cracks will form in the asphalt barrier because of the embrittlement and recurring stresses related to seismic events. The increased cracking in the asphalt barrier and the vault will allow more infiltrating water to flow through the engineered disposal system. Advection overcomes diffusion as the primary mechanism by which radionuclides leave the Grout Disposal Facility.

(a) End view cross-section of vault.

(b) Schematic of roof plank joint orientation and distribution

S9211085.52

Figure 3.9. Schematic Drawing Showing the Degradation During the 0- to 100-Year Period, and an Exploded View of Roof-Plank Joint Orientation and Distribution

S9211085.53

Figure 3.10. Schematic Drawing Showing the Degradation During the 100- to 10³-Year Period, and an Exploded View of Cracking on Concrete Surfaces

In the following sections, degradation of the components of the disposal system is discussed in more detail. The flow and transport properties of the components as they relate to the retention and movement of radionuclides in the disposal system are also described.

3.3.3 Grout and Concrete Vault

This section describes the conceptual model and data used to predict the flow of water and transport of contaminants in cementitious components of the Grout Disposal Facility (i.e., steel-reinforced concrete and grout). Transport models and data for the grout waste form essentially constitute the release model for grout. Steel-reinforced concrete is included in the vault and catch basin of the engineered disposal system. The conceptual model for the movement of contaminants within both grout and concrete includes process models for simultaneous advection and diffusion. Effective diffusivities were measured in the laboratory and values derived for each radionuclide in the grout waste form. Sorption of chemicals and radionuclides in the media by precipitation or adsorption was modeled for the grout waste form, but not for concrete. Values for and sources of model parameters are presented.

Advection within cementitious materials was modeled using the van Genuchten-Mualem model (see Section 3.2.5.1 and Appendix P, Section P.1.1), which was originally developed to describe the water retention and relative permeability of unsaturated soils. The basis for the parameters used in this model of grout will be briefly described here and is more thoroughly presented in Appendix J. Appendix J discusses hydraulic properties of natural and engineered materials. Note that the clean grout (see Section 2.6.1 and Figure 3.2) filling the space between the radioactive grout and the ceiling of the vault is assigned the same flow and transport properties as radioactive grout; however, its initial waste concentration is set to zero.

3.3.3.1 Initial Release Model for Grout

This section describes the conceptual model for transport within the grout waste form. This model is essentially the release model for contaminants. The conceptual model for the movement of contaminants within grout includes process models for simultaneous advection, diffusion, and sorption. Values for and sources of model parameters are presented.

Diffusion in Grout. Data for simulating molecular diffusion in the grout are based on data obtained in laboratory leach tests. Semi-infinite solid diffusion leach models were assumed to be appropriate models for describing the release of trace contaminants from cement waste forms (e.g., Dayal, Schweitzer, and Davis 1984; Sambell, Smitton, and Elsdon 1982). Based on laboratory leach tests on small-scale (generally cylindrical) solid waste forms, an effective diffusion coefficient for each radionuclide or chemical species in the grout waste form was calculated.

Table 3.2 lists specific radionuclides and chemical species for which effective diffusion coefficients for grout were measured. The grout formulation used for each of the wastes in Table 3.2 was specific to that waste. The grout formulation may be optimized for each waste type that is processed through the Grout Treatment Facility. The data for leaching of TcO_4^- and I^- from a variety of grouted waste forms is provided in Appendix P, Section P.2.1.1.

Table 3.2. Specific Species/Grout Combinations for Which Effective Diffusion Coefficients Were Measured

PSW Grout ^(a)	CRW Grout ^(b)	Tank 106-AN Grout ^(c)	DSSF Grout ^(d)	PSW Cores ^(e)
Na	Na	$\text{NO}_3^{(f)}$	^{99}Tc	Al
K	K	$\text{NO}_2^{(f)}$	^{125}I	Ca
^{54}Mn	F	$\text{Cl}^{(f)}$	Cr	Na
^{60}Co	NO_3	F	$\text{Na}^{(g)}$	SO_4
^{85}Sr	SO_4	$\text{Na}^{(f)}$	$\text{NO}_2^{(g)}$	^{60}Co
^{137}Cs	^{14}C	Mo	$\text{NO}_3^{(g)}$	^{137}Cs
^{14}C	^{99}Tc	Ni	Se	
Cd	^{137}Cs	Cr		
Hg	^{85}Sr	^{241}Am		
Ag	^{241}Am	^{137}Cs		
Se	Pu	^{129}I		
I	I	^{90}Sr		
Cr	^{99}Tc	$\text{SO}_4^{(f)}$		
Pb	^{60}Co			
^{99}Tc	^{79}Se			
As	PO_4			
U				
SO_4				
Al				
Ca				

(a) Phosphate/sulfate waste (Serne et al. 1987, Serne et al. 1989).

(b) Cladding removal waste (Serne and Wood 1990).

(c) Waste from a double-shell tank at Hanford grouted with the formulation developed for DSSF (Serne et al. 1989).

(d) Double-shell slurry feed (Serne 1990, Serne et al. 1992, Tallent et al. 1988).

(e) Martin and Lokken (1992).

(f) Lokken (1992).

(g) Lokken, Martin, and Shade (1992).

The effective diffusion coefficient obtained from a leach test incorporates the effects of solubility, tortuosity, volume fraction pore solution (for determining driving force), and molecular diffusivity in the pore solution into a single parameter that can be used with the total volume-based concentration. Some constituents have very low solubility or experience sorption onto the solid surfaces of the grout. These species have low release rates in leach tests, resulting in low effective diffusion coefficients. Releases of species with significant sorption or solubility limitations are not diffusion controlled. The low concentration of the species in the pore solution results in effective diffusion coefficients with lower values than can be explained by the pore structure of the grout. Modeling the diffusional release of these species with an effective diffusion coefficient would provide reasonable results if diffusion were the only release mechanism. However, the degradation of engineered structures is considered in this performance assessment and the impact of the advection of contaminants from grout is evaluated. Therefore, the concentration of contaminants in the pore solution is an important variable. Species with significant sorption or low solubility are released by advection at lower concentrations and lower rates than fully soluble species. Release from grout was modeled by using a sorption model to represent sorption and solubility constraints. To model release from the grout, the effective diffusion coefficient has been separated into its diffusion- and sorption-related components.

The effective diffusion coefficients measured in leach tests are influenced by various factors as shown below:

$$D_{e1} = \frac{TD_m}{R_i} \quad (3.6)$$

where D_{e1} = effective diffusion coefficient (L^2/T) based on grout volume concentration

T = tortuosity factor (dimensionless)

D_m = the molecular diffusion coefficient (L^2/T) of the solute in an aqueous solution

R_i = R for species i (see Section 3.2.5.2 and Appendix P, Section P.1.2) (dimensionless).

Sorption in Grout. For all species in the grout waste form, the molecular diffusivity in the pore solution was assumed to be $2.5 \times 10^{-5} \text{ cm}^2/\text{s}$. For nitrate the R is expected to be 1.0, indicating that the nitrate is fully soluble and mobile in the pore solution. From an observed effective diffusion coefficient for nitrate of $5 \times 10^{-8} \text{ cm}^2/\text{s}$, the tortuosity factor for grout (ambient temperature curing) was calculated from Equation 3.6 as 0.002. The tortuosity was assumed to be a physical property of the grout, not a species-specific property. Then, from the grout tortuosity factor and the measured effective diffusion coefficients for other species, the R for these species were calculated.

All contaminants analyzed were sorted into four groups of radionuclides and chemicals representing transport groups with a single effective diffusion coefficient. All species in a group have an effective diffusion coefficient less than or equal to the diffusivity assigned to that group. This treatment leads to higher-than-measured diffusion coefficients for some species, but significantly reduces the amount of modeling required to simulate the release and transport of the inventory.

The bulk of the data for effective diffusion coefficients exists for curing at ambient temperature. However, experimental work (Lokken 1992) has indicated that the diffusion coefficient for nitrate in grout cured at high temperature over long time periods increases to values approaching $1 \times 10^{-6} \text{ cm}^2/\text{s}$.^(a) Curing at elevated temperature is an expected condition in the Grout Disposal Facility. In the case where the effective diffusion coefficient in the grout increased because of high-temperature curing, the change was assumed to result from a change in the grout tortuosity. To make this adjustment, the tortuosity factor for nitrate was recalculated using the degraded diffusion coefficient value of $1 \times 10^{-6} \text{ cm}^2/\text{s}$, which is higher than that used originally by a factor of 20. This approach results in a tortuosity factor of 0.04. From the grout tortuosity factor and the previously calculated R (which are assumed to remain valid), the transport properties for the degraded or high-temperature case were calculated for each species. Prior to use in the numerical model, the R values were converted to R_d based on the bulk density (1.105 g/cm^3) and saturated porosity (0.5781) of the grout. (For additional information, see footnote to Table 3.15.)

Before applying the measured grout effective diffusion coefficients in the computer model, an adjustment was made to account for the fact that the driving force is calculated in the model on a pore water basis and the leach test effective diffusion coefficients were based on total grout volume. This conversion was made by multiplying the leach test effective diffusion coefficients by the volume fraction of pore water as shown in Equation 3.7.

$$D_{e2} = \theta D_{e1} = (\theta T D_m)/R \quad (3.7)$$

where D_{e2} = effective diffusion coefficient (L^2/T) based on grout pore water concentration

θ = volume fraction of pore water in grout taken as 0.5781 (Appendix J).

These properties for the radionuclides evaluated in the performance assessment are listed in Table 3.3.

This approach to modeling the release from grout is correct if the mechanism for reduced effective diffusion coefficients is sorption. However, a sorption model was used to simulate the slow release of both sorption-controlled and solubility-controlled species. If the release is controlled by solubility, an

(a) Effective diffusion coefficient based on bulk grout concentration.

Table 3.3. Initial Source Parameters for the Asphalt Barrier, Concrete Vault, and Grout in the Nondegraded Engineered System (Grout properties degraded because of high-temperature curing.)

	Groups of Contaminants	$D_{e1}^{(a)}$ (cm ² /s)	$D_{e2}R^{(b)}$ (cm ² /s)	$R^{(c)}$ (-)	R_d (ml/g)
Barrier	All	NA	1×10^{-10}	1.0	0
Concrete	All	NA	5×10^{-8}	1.0	0
Group 1A ^(d)	³ H, ¹⁰³ Ru, ¹⁰⁶ RuRh, ¹²⁵ Sb, ¹²⁹ I	1×10^{-6}	5.781×10^{-7}	1.0	0
Group 2A,B	⁹⁹ Tc, ⁹⁴ Nb, ⁹⁵ Nb	2×10^{-7}	5.781×10^{-7}	4.82	2
Group 3A,C	⁶⁰ Co, ⁶³ Ni, ⁷⁹ Se, ⁹⁰ Sr, ¹¹³ Sn, ¹²⁶ Sn, ¹³⁴ Cs, ¹³⁵ Cs, ¹³⁷ Cs, ²²⁶ Ra, ²³⁷ Np	4×10^{-9}	5.781×10^{-7}	240	125
Group 4A,D	¹⁴ C, ²³⁴ U, ²³⁵ U, ¹³⁸ U, ⁹⁵ Zr, ¹⁴⁴ CePr, ¹⁵² Eu, ¹⁵⁴ Eu, ¹⁵⁵ Eu, ²³⁰ Th, ²³⁸ Pu, ^{239/240} Pu, ²⁴¹ Am, ²⁴¹ Pu, ²⁴² Pu, ²⁴³ Cm, ²⁴⁴ Cm	2×10^{-10}	5.781×10^{-7}	5020	2625

NA = not applicable.

- (a) Concentration driving force based on bulk media concentration. Includes effect of degradation from high-temperature curing. Values obtained from ambient temperature curing have diffusivities that are lower by a factor of 20.
- (b) Represents the diffusive mobility of ions in media, neglecting sorption effects. This was the diffusive parameter used in code calculations. Concentration driving force is defined in the pore fluid of grout/concrete or asphalt phase in diffusion barrier. For grout, separated into $D_{e2}R = \theta TD_m$ where θ = volume fraction pore fluid or volumetric water content, T = tortuosity factor, D_m = molecular diffusion coefficient in pore solution.
- (c) R values were assigned and from them R_d values were determined. Because of rounding, the R_d and R values do not agree precisely. The R_d values were used in all code calculations.
- (d) Values used for the cold grout cap are identical to those for contaminated grout. Group numbers identify grout R . Letters refer to divisions within the group number for different soil R_d .

advective release (pore fluid advecting through grout) will occur at a constant concentration until the solid phase is depleted. With a sorption model, the concentration will drop over time as the inventory is released, maintaining a constant ratio between solid and liquid phase contaminant concentrations.

Serne et al. (1992) conducted experiments on grout samples in which the tracer concentration was varied to determine the leaching mechanism for iodine-129, selenate (SeO_4^{2-}), and pertechnetate

($^{99}\text{TcO}_4^-$). They concluded that solubility mechanisms were not important for release of these species. Release of iodine-129 was controlled by diffusion and linear adsorption. In this performance assessment, iodine-129 was assumed not to be sorbed. Release of $^{99}\text{TcO}_4^-$ and SeO_4^{2-} was controlled by diffusion and nonlinear adsorption. The nonlinear adsorption results in a higher diffusivity at higher concentrations because of saturation of preferred adsorption sites. Leach tests for $^{99}\text{TcO}_4^-$ were performed at concentrations of 100 to 10,000 $\mu\text{Ci/L}$ while the waste average concentration in grout is 50 $\mu\text{Ci/L}$. Therefore, the sorption of $^{99}\text{TcO}_4^-$ within the grout vault will be greater than observed in leach tests in which a higher concentration was used. Therefore, the mobility assigned to the key radionuclides (technetium-99 and iodine-129) in the grout waste form is believed to be conservative.

The other important radionuclide is neptunium-237. The peak dose from neptunium-237 is generally of similar magnitude to that for iodine-129 and technetium-99. However, the sorption properties of neptunium-237 in the grout and soil substantially delay the arrival and spread the peak over a longer period of time. From an integrated dose standpoint, the neptunium peak is actually larger than the technetium-99 and iodine-129 peak. No data are available on the leach behavior of neptunium-237 from Hanford grout. The values used for sorption of neptunium-237 were selected to be conservative based on expert judgment. A subsequent review of data available for neptunium-237 has confirmed that these values are conservative. Appendix P (Section P.3.2.1) provides a summary of literature reviewed.

Advection in Grout. Before the asphalt barrier degrades, water flow into and through the grout is limited by the low hydraulic conductivity of the asphalt barrier. However, as the engineered system degrades over time, the hydraulic properties of the grout become important.

The hydraulic properties of grout used in this performance assessment are based on experimental measurements made on grout samples obtained from a pilot-scale grout production test using a nonradioactive simulated DSSF waste. The water retention characteristic curve is represented by van Genuchten-Mualem model parameters and is based on data from nine samples. The parameters were determined from a fit of data generated by a thermocouple psychrometer. Before fitting the data, an adjustment was made to extract the depression in vapor pressure apparent in the data due to the high ionic strength of the grout. This was done to minimize the influence of vapor pressure depression in the unsaturated zone simulations that did not reflect the high ionic strength of the grout. The saturated hydraulic conductivity of the grout was determined from measurements on three samples in a constant-head permeameter. Unsaturated hydraulic conductivities were calculated from the water retention characteristic using the Mualem relationship (Appendix P, Section P.1.1). Gravimetric water contents were used along with the average bulk densities to determine the sample porosities. Table 3.4 lists a summary of the initial parameter values for intact grout and the cold cap. Appendix J provides details of the measurements and data reduction.

Flow and Transport in Noncontaminated Grout. After grout containing wastes has been poured into a vault and cured for 30 days, any liquid remaining on the grout surface will be removed. The space between the concrete cover blocks and the contaminated grout surface will be filled with a noncontaminated grout to eliminate the possibility of subsidence. All flow and transport properties for this grout are

Table 3.4. Initial Hydraulic Properties for Grout

	$\theta_s^{(a)}$	$\theta_r^{(b)}$	$\alpha \text{ (cm}^{-1}\text{)}^{(c)}$	$n^{(d)}$	$K_s^{(e)} \text{ (cm/s)}$
Grout/Grout Cap	0.5781	0.0000	1.08×10^{-5}	1.650	1.47×10^{-8}

- (a) θ_s = saturated water content (volume fraction water when saturated cm^3/cm^3).
 (b) θ_r = residual water content (cm^3/cm^3).
 (c) α = reciprocal of air entry pressure ($1/\text{cm}$).
 (d) n = dimensionless curve-fitting parameter.
 (e) K_s = saturated hydraulic conductivity (cm/s).

assumed to be the same as those for the contaminated grout. The only difference in the simulation of this region is that the noncontaminated grout does not initially contain contamination. In the waste grout, a high water-to-cement ratio increases the amount of liquid waste that can be disposed of in a single vault. The noncontaminated grout may be formulated with a lower water-to-cement ratio, thereby improving its hydraulic and transport properties compared to the contaminated grout.

3.3.3.2 Initial Flow and Transport Properties of the Concrete Vault

Models and associated parameters defining the flow of water and transport of contaminants are needed to model the migration of contaminants through the concrete vault. The basis for the initial value of each parameter is described below. Changes to these properties over time as the reinforced concrete degrades are described in Section 3.3.3.4, which discusses concrete degradation and geochemistry.

Diffusion in Concrete. An effective diffusion coefficient for each contaminant in the concrete was needed to model transport of the contaminants through the vault walls. The values used in this performance assessment were obtained from published literature and compared with measured values of diffusion through cement-based waste forms.

Savannah River Laboratory (Albenesius and Wilhite 1986) used an effective diffusion coefficient for the concrete vault of $5 \times 10^{-8} \text{ cm}^2/\text{s}$ for all species in a performance assessment for cemented waste. Muurinin et al. (1983) determined effective diffusion coefficients for cesium and strontium of 3×10^{-9} and $6.9 \times 10^{-12} \text{ cm}^2/\text{s}$, respectively, in construction concrete. They compared these values with others reported in the literature (strontium-90 at 10^{-8} to $10^{-10} \text{ cm}^2/\text{s}$ and cesium-137 in the range of 10^{-9} to $10^{-10} \text{ cm}^2/\text{s}$).

In this performance assessment, a single effective diffusion coefficient of $5 \times 10^{-8} \text{ cm}^2/\text{s}$ with the driving force defined in the concrete pore solution was assumed for all species in the concrete (see Table 3.3). Lower effective diffusion coefficients may exist for many species such as strontium-90 and cesium-137, as described above. However, no credit was assumed for sorption or precipitation within the

concrete. Strontium-90 is known to form carbonates and hydroxides under the high pH conditions that exist in the grout and concrete (Lindsay 1979). Thus, the effective diffusion coefficient for strontium-90 within the concrete was expected to be lower than that for mobile anions. Similarly, cesium-137 is adsorbed by many materials and may have a lower effective diffusion coefficient in concrete.

Advection in Concrete. The hydraulic properties of the concrete are based on experimental measurements of six concrete samples received from Sandia National Laboratory (SNL). Water retention properties are represented by van Genuchten-Mualem model parameters. The parameters were determined as they were for grout (see Section 3.2.5.1 and Appendix P, Section P.1.1). Appendix J provides details of the measurements. The degree to which the concrete in the grout vaults is similar to the concrete received from SNL is unknown. To address this problem, an attempt was made to compare the hydraulic conductivity to literature values.

Work by Whiting (1988) determined that the water-to-cement ratio is a key variable influencing the permeability of concrete, with permeability increasing with increasing water-to-cement ratios. The concrete specification for the construction of the grout vault indicates a maximum water-to-cement ratio of 0.42. The mix design of the concrete actually used a water-to-cement ratio of 0.34.

The permeability observed by Whiting for a concrete with a water-to-cement ratio of 0.4 was 2.6×10^{-11} cm/s. The permeability was below detection limits for a concrete with a 0.288 water-to-cement ratio. The permeability for concrete with a water-to-cement ratio of 0.4 is a factor of 14 smaller than that used in the performance assessment. The content of cementitious material was 642 lb/yd³ cement for the 0.4 water-to-cement ratio for the concrete used in Whiting's work, and 529 lb/yd³ cement plus 133 lb/yd³ fly ash for the vault concrete. The gradations for the two mixes were similar. The gradations of the total aggregate (combined fine and coarse aggregate) are compared in Table 3.5. The values for the vault are a single sieve analysis; actual values fall within an allowed range on aggregate sizes. Although the concrete used by Whiting and that used for the vault construction have similarities, there are differences that must be considered. The air void content was 5.6% for the vault concrete and 2.3% for the Whiting concrete. However, the general similarity of the concretes and the fact that the value selected for hydraulic conductivity is 14 times lower than the literature value indicates that the value selected for the concrete is reasonably conservative. Table 3.6 provides a comparison of the saturated hydraulic flow properties for concrete in the performance assessment to the values for the Whiting concrete. Table 3.7 summarizes the hydraulic parameters for concrete applicable during periods of high integrity. In some cases, initial concrete water retention properties were altered to facilitate modeling of degradation (see Section 3.6.3.4 and Appendix P, Section P.1.1).

3.3.3.3 Degradation of Grout

A considerable and continuing effort exists to formulate grout and measure its original properties. Standard methods have been used to determine the leachability of a variety of grout formulations and the unsaturated hydraulic properties of a single sample. However, the long-term hydraulic, transport, and attenuation properties of the grout are an area of considerable uncertainty. During the curing process for

Table 3.5. Comparison of Aggregate for the Vault Concrete Mix Design to Literature-Reported Values for Concrete

<u>Sieve Size</u>	<u>Wt% Passing 0.4 Water-to- Cement Mix^(a)</u>	<u>Wt% Passing for Vault Construction^(b)</u>
1"	100	100
3/4"	100	95.7
3/8"	71.1	69.9
No. 4	40.5	53.2
No. 8	34.2	30.3
No. 16	28.3	22.4
No. 30	15.6	15.4
No. 50	3.4	4.3
No. 100	0.4	0.8
No. 200	not specified	0.4

(a) Whiting (1988).

(b) Submittal Approval to David A. Mowat Company
5-9-90 from Tom Morton, Kaiser Engineers
Hanford. KEH No. 5162 (B-714). Submittals
064.A.102, 064.A.103, 0.64.A.104, 0.64.A.105 for
concrete mix design.

Table 3.6. Comparison of Saturated Hydraulic Properties for Concrete: Hanford and Whiting^(a)

<u>Concrete Property</u>	<u>Performance Assessment</u>	<u>Whiting Concrete</u>
K_s	3.75×10^{-10} cm/s	2.6×10^{-11} cm/s
θ_s	0.2258	0.113

(a) Whiting (1988).

Table 3.7. Initial Hydraulic Properties for Concrete

<u>Medium</u>	<u>θ_s</u>	<u>θ_r</u>	<u>α (cm⁻¹)</u>	<u>n</u>	<u>K_s (cm/s)</u>
Concrete	0.2258	0.00	7.61×10^{-6}	1.393	3.75×10^{-10}

grout, a cementitious material with a high porosity (55% to 60% by volume), a very fine pore structure, and continuously connected pore space is formed. While grout cures and excess liquid is removed in a matter of months, the actual curing process continues indefinitely, and, in general, the hydration products of the cement and fly ash continue to be formed (i.e., hydrated calcium silicate and calcium hydroxide). During hydration, the hydrated cement gel material incorporates pore water and forms precipitates on the surfaces of existing solids that border the pores. Thus, the pore structure will become finer with time as the curing process continues to form hydration products (Dames and Moore 1989).

Care was taken in formulating grout to minimize the potential for formation of expansive minerals that could cause extreme internal stresses and cracking. The formulation efforts attempted to minimize the depletion of OH and the formation of gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) within the grout. Infiltrating water may import sulfate into the concrete and grout materials; however, sulfate concentrations in water (Dames and Moore 1989) contacting Hanford soils are below concentrations associated with the formation of significant amounts of expansive minerals.

Grout is designed to exhibit relatively good volume stability indefinitely; however, it is not designed to develop the compressive strength and other structural properties of concrete. Consequently, the grout could degrade as the reinforced-concrete vault degrades and external (e.g., seismic) loads are transferred to the grout monolith. Because it will not have sufficient structural strength to bear these loads, it is anticipated that the grout monolith will experience cracking, fracturing, or a generalized breakup in response to vault degradation (i.e., the timing of grout degradation may correspond to the timing of steel-reinforced concrete vault degradation). The severity of such a degradation process (i.e., timing and magnitude) and the uniformity of associated cracks are unknown and have not been forecast from first principles. However, the grout monolith could experience stresses at points where the vault experiences through-wall cracks because of the inability of the vault structure to bear loads at these locations. It is possible that localized crushing would occur at locations directly opposite corroding rebar and that crushing would be limited to the grout surface. These weakened regions on the grout monolith could then be impacted by seismic loadings, and extensive cracks could form. Thus, as a first approximation, one could assume the grout monolith cracks along planes defined by construction joint cracks in the reinforced-concrete vault.

Because of the composition of Hanford soils, natural infiltration percolating into the vault and the grout waste form through fine cracks is anticipated to carry with it dissolved carbon dioxide (CO_2). The pH of the infiltrating water will be nearly neutral, but upon reaching either the concrete or grout, the high pH pore fluids will cause the CO_2 to react with calcium hydroxide (CaOH) and precipitate calcium carbonate (CaCO_3) abruptly in the pores or cracks that conduct the infiltrating waters. This mineral precipitation could cause plugging of cracks at high pH interfaces, or a more general filling of cracks along crack surfaces.

Infiltrating water from the surrounding soil environment is expected to be imported in limited quantities. Thus, infiltrating water is expected to affect only a small portion of the grout monolith. Typically, impacts are anticipated at the outer surface of the grout where infiltrating waters bearing dissolved CO_2

first contact the grout, and in the cracks of the monolith where waters may preferentially flow and diffuse. These impacts will be limited to the vicinity of breaks in the concrete and asphalt barrier, which provide the pathway for the infiltrating water and chemicals to convect and diffuse to the grout surfaces and cracks. Note that portions of the grout monolith characterized by the discharge of pore water to the surrounding engineered system should not be associated with the precipitation of calcium carbonate, but should be associated with the formation of hydration products. If grout pore water reaches the vadose sediments with its high pH preserved, calcium carbonate could precipitate in the sediments.

The overall long-term conceptual model is one of a fractured grout monolith, its matrix made up of blocks of unfractured grout and its fractures or cracks partially or completely plugged with calcium carbonate or hydration products (hydrated calcium silicate and calcium hydroxide). The continuing formation of hydrated calcium silicate and calcium hydroxide during long-term grout cure should result in a finer pore structure with time in blocks of unfractured grout. Thus, the unsaturated hydraulic performance of the unfractured grout would be conservatively modeled using the original (i.e., freshly cured) unsaturated hydraulic properties measured for grout. The true hydraulic performance of the fractures will depend on the pore structure associated with the fracture openings. A number of alternatives exist, e.g.,

- cracks are open and represent a discontinuity in the unsaturated material
- cracks are plugged at points where infiltrating waters contact them (e.g., at the pH front), and open elsewhere
- cracks are filled throughout their volume with calcium carbonate as a result of complete contact with infiltrating water
- cracks are filled with hydrated calcium silicate and calcium hydroxide formed during long-term cure of the adjacent unfractured grout block
- cracks are filled with a combination of calcium carbonate at exterior surfaces, and hydrated calcium silicate and calcium hydroxide on interior surfaces.

Based on our knowledge of the chemistry of grout, and, in particular, the long-term character of its curing process, it is assumed that minerals do form in cracked grout. These minerals are deposited in cracks, and can be envisioned as either fine-grained deposits of calcium carbonate along crack surfaces where waters of different pH would contact one another, or as fine-grained deposits of hydrated calcium silicate and calcium hydroxide formed on grout surfaces that border cracks. As a result, the crack surfaces will likely be coated, if not filled, with fine mineral deposits.

3.3.3.4 Degradation of Concrete

The vault, catch basin, and sump enclosure are all constructed of steel-reinforced concrete. No near-surface faults nor soil liquefaction potentials have been identified in the geological environment sur-

rounding the grout vault. The potential for seismic stresses to affect the buried structure is low (see Section 2.1.9). This was demonstrated by a 0.35 G three-dimensional seismic evaluation of a symmetric quarter of the vault in its final configuration (i.e., filled with grout) (B. V. Winkel, 1992, private communication^(a)).

The processes anticipated to cause degradation of the reinforced-concrete material are summarized as follows (see Appendix Q):

Process or Mechanism	Associated Degradation
<ul style="list-style-type: none"> • Short-term seismic stress 	<ul style="list-style-type: none"> • A three-dimensional symmetric quarter of the vault was analyzed for a 0.35 G acceleration event and it demonstrated negligible impact on the design structure.
<ul style="list-style-type: none"> • Long-term seismic stress 	<ul style="list-style-type: none"> • Extension of partial cracks and creation of through cracks in the aged and rebar corroded reinforced-concrete structures.
<ul style="list-style-type: none"> • Short-term rebar corrosion 	<ul style="list-style-type: none"> • Short term rebar corrosion is unlikely because of 1) cathodic protection, 2) high pH level, 3) low permeability of concrete, 4) relatively low chlorides, and 5) presence of asphalt liner separating grout from concrete vault.
<ul style="list-style-type: none"> • Long-term rebar corrosion 	<ul style="list-style-type: none"> • Loss of integrity of reinforcing steel and the associated susceptibility to seismic load failure, and localized cracking of the concrete surface adjacent to rebar and the associated change in hydraulic characteristics of concrete surfaces.
<ul style="list-style-type: none"> • Overburden loads 	<ul style="list-style-type: none"> • Cracks in unreinforced roof plank joints.
<ul style="list-style-type: none"> • Corrosion of water stops 	<ul style="list-style-type: none"> • Cracks at construction joints in walls and floors.
<ul style="list-style-type: none"> • Short-term drying shrinkage 	<ul style="list-style-type: none"> • Relatively tight cracks limited to the surface caused by the different drying rates of exterior and interior concrete.

(a) Winkel, B. V. 1992. "Grout Vault Asphalt Barrier Seismic Adequacy, Preliminary Report." Memo from B. V. Winkel to R. K. Sanan, BVW-23420-92-001, Westinghouse Hanford Company, April 21, 1992.

Process or Mechanism	Associated Degradation
• Short-term thermal stress	• Tight cracks on the surface of the concrete produced by relatively high thermal stress levels resulting from high thermal gradients caused by heat of hydration during grout cure and cesium decay.
• Chemical reactions	• While some long-term chemical degradation is likely, the consequences should be minimal because chemical degradation reaction products will tend to bond to the concrete and fill cracks, and relatively few pore volumes of potentially chemically degrading waters are anticipated to flow through the structure. Some resealing is expected in seismically induced crack openings.

The above-listed mechanisms and processes will take their toll over the extended life of the waste disposal system (i.e., 10^5 years); however, the reinforced-concrete structure is assumed to exhibit relatively high integrity for 1,000 years. This level of assumed integrity is a result of the initial integrity and volumetric stability of the structure, the fact that the structure is buried and thus isolated from the environmental extremes, and the alkaline character of the wastes. A principal mechanism leading to the degradation of the integrity of the reinforced-concrete vault is the corrosion of the reinforcing steel and waterstops caused by the advection and diffusion of waste constituents to the steel surfaces. While the long-term performance of the asphalt liner inside the vault cannot be quantified, its presence and the role it will play in impeding the migration of contaminants to the steel should be recognized.

Two classes of cracks are apparent from the preceding description: surface cracks and through-wall cracks. Cracks are anticipated to occur on all concrete surfaces in response to rebar corrosion. Degradation of these surfaces could create preferential flow paths from a saturated flow perspective, and capillary breaks or barriers to flow from the unsaturated flow perspective. However, the interior portion of the concrete wall (i.e., concrete between the interior and exterior rebar mesh) should retain relatively high integrity and low hydraulic conductivity. The integrity of the interior portion of the walls may be adversely affected by the presence of rebar stirrups used to ensure the proper spacing of the rebar near the exterior and interior surfaces. Releases will not occur solely because of surface cracks. On the other hand, once through-wall cracks appear, they may represent conduits for the release of pore liquid from the grout through the reinforced-concrete vault.

With the exception of the joints between roof-plank sections, the structure is assumed to function as designed for 100 years. During the 100- to 1,000-year period, additional degradation of the roof-plank joints is assumed to be accompanied by degradation of construction joints and the onset of concrete surface degradation resulting from rebar corrosion. In addition to greater degradation of joints and concrete surfaces, through-wall cracks (1-mm on 1-m square grid) induced by rebar corrosion and seismic events

are forecast to appear during the 10^3 - to 10^4 -year time period. During the final time period (10^4 to 10^5 years), which represents the indefinite future for this performance assessment analysis, cracks existing after 10^4 years become wider (e.g., 2 mm) and through-wall cracks caused by rebar corrosion and seismic events become more closely spaced (e.g., 0.5-m square grid).

3.3.4 RCRA Flow Grid, Catch Basin, Sump, and Thermal Insulation Board

A RCRA secondary containment requirement is satisfied by the flow grid and catch basin elements of the disposal system design. The flow grid or drainage net (see Figures 2.30 and 3.10) is composed of high-density polyethylene (HDPE) strands bonded or cast to form a minimum 5-mm-thick mesh. Two sheets of flow grid (total minimum thickness of 1 cm) are placed on the outer surface of the reinforced-concrete vault. The flow grid is designed to direct any flow of liquids that might escape from the grout through the steel-reinforced concrete vault to the catchment basin beneath the vault. This is followed by a 60-mil (1.5-mm) HDPE curtain and a layer of geotextile. The flow grid is designed to direct any leachate from the vault to the catch basin. The basin is filled with uniformly sized clean gravel. Flow directed to the basin drains to the sump, which will be pumped to remove any drainage from the vault during the first 30 years of vault service. The real function of this component of the engineered system is to contain and capture liquids until the grout has set and free liquid is removed, a period of time measured in months.

3.3.4.1 RCRA Flow Grid

The RCRA system is designed for a service life of 30 years. It is assumed that the components of the system will function as a preferred path for any leachate from the waste disposal system for a much longer period. The HDPE flow grid material should be chemically inert in the grout vault environment, even in the presence of radiation. Radiation exposure causes crosslinking of polymer chains, thus reducing break strength and break elongation. These effects occur in the Mrad (10^6 rad) range, and become most pronounced at doses of 16 to 37 Mrad. However, location of the flow grid and curtain outside the concrete wall reduces the dose to about 14 rad. This dose will not have any effect on the HDPE material. Although HDPE materials have been in existence only about 35 years, plastics experts^(a) believe that properties of HDPE material should change very little, even for thousands of years. The only significant physical modification envisioned is some reduced thickness in the flow net (originally 1 cm) because of the viscoelastic (creep) response to external pressures. As noted in the following description of reinforced concrete, forces originating in the corrosion of steel reinforcement may impact the flow path material but not the overall conclusion that a vertical flow path will exist along the walls of the vault for thousands of years.

(a) N. R. Gordon, PNL, personal communication.

In all of the simulations where the HDPE flow grid was included, its hydraulic properties were assumed to be those of backfill soil. Hydraulic properties were not measured for the flow grid. Hydraulic properties for backfill soil were assumed because of the relatively high hydraulic conductivity of backfill soil compared with other components of the engineered system.

3.3.4.2 Catch Basin and Sump

The catch basin is composed of reinforced concrete. It is assumed that the basin will degrade as the reinforced-concrete vault is forecast to degrade. Relative movement between the drainage basin and sump pit should be minimal because of the robust structural interface connecting the two structures. The interface is constructed of reinforced concrete reaching a thickness of 4.572 m (15 ft) (see Figure 2.30 and Appendix O). A 26-in.-outside diameter riser made of carbon steel connects the sump to the land surface. This riser protrudes through the asphalt barrier above the sump. Initially, the sump is filled with gravel to provide volume stability. During closure of the facility, the riser and sump will be backfilled with a grout slurry. Corrosion of the carbon steel may provide a release pathway if saturated conditions were to exist in the catch basin and sump, and if the asphalt barrier continued to act as an impermeable barrier (i.e., if the asphalt barrier represents a perfect bathtub). It is not envisioned that the basin and sump will function in this way; rather, it is expected that liquid under positive pressure (i.e., saturated ponding in the catch basin and sump) would drain through the intact or degraded engineered system before significant levels of ponding could occur within the structure.

3.3.4.3 Thermal Insulation Board

In addition to the 1-cm flow net, a 2.54-cm (1-in.) layer of relatively porous thermal insulation board is placed between the flow net/HDPE curtain/geotextile and the asphalt barrier, as illustrated in Figure 3.10. This insulation board insulates both the steel-reinforced concrete and the HDPE materials from the thermal shock of the hot asphalt barrier material as the material is placed and compacted during construction.^(a) An estimate for disintegration of this wood-based material is based on knowledge of wood disintegration in the anticipated environment (asphalt coated, low moisture, low air availability). The best estimate is that disintegration will be slow. Disintegration of this material is forecast to occur in the 100- to 1,000-year time period and will lead to either the formation of a void between the flow net and asphalt

-
- (a) Specifications (Kaiser Engineers Hanford Company 1989) for the asphalt barrier call for the mix temperature not to exceed 171°C (340°F) at the batch plant, to be not less than 126.5°C (260°F) at the rear of the laydown machine during placement, and to be not less than 88°C (190°F, average lift mix temperature) before roller compaction is completed. Data collected when the asphalt barriers around vaults 218-E-16-102 through -105 were placed demonstrated that placement temperature was between 143.5°C and 149°C (290°F and 300°F). Design specifications for the grout formulation call for grout cure to occur at or below 90°C. Estimates of grout temperature resulting from the decay of radionuclides indicate a broad temperature plateau of approximately 55°C (131°F) for a 35- to 50-year period, followed by a gradual decline to ambient temperatures after 200 to 300 years.

barrier wall, or to the gradual and continual compression of the thermal board in response to external loads. In either case, it is anticipated that slumping of the ductile asphalt barrier wall into the space previously occupied by high-integrity thermal insulation board will be sufficient to produce cracks in the vicinity of wall-roof joints in the asphalt barrier. As with the HDPE flow grid, the hydraulic properties of the thermal insulation board were assumed to be the same as those for backfill soil.

3.3.5 Asphalt Barrier

This section presents a description of the initial state and dominant transport processes of the asphalt barrier, an assessment of water-vapor diffusion, a forecast of degradation leading to cracks, and a description of other degradation mechanisms contributing to surface degradation. The conceptual model for transport of contamination through either an intact or degraded asphalt barrier includes simultaneous advection and diffusion. Sorption is not modeled in the barrier, representing a conservatism in the analysis. The flow of water through the asphalt-barrier media was modeled using the unsaturated flow characteristics of the van Genuchten-Mualem model. In addition to the advection-diffusion of contaminants, the potential migration of water vapor as a mechanism to transport moisture to the concrete vault and waste was considered. The conceptual models for the intact and degraded asphalt barrier are described and model parameters are presented.

The van Genuchten-Mualem characterization of unsaturated hydraulic properties was adopted for application to the asphalt barrier. The intact asphalt barrier is virtually impermeable to the flow of water because water doesn't wet asphalt. The wetting properties of the fluid-solid interface are particularly important in the unsaturated zone setting, where surface tension and capillary forces play a dominant role in water flow. In addition, the asphalt initially has a very small porosity (≤ 4 vol%) available for water flow, and the hydraulic conductivity of water for asphalt is very low. The low porosity undoubtedly presents a tortuous and largely unconnected flow path for liquid water within the asphalt. This influences both the advection and diffusion of contaminants because the high likelihood of a disconnected water pathway implies no contaminant migration in the liquid water phase. Thus, the advective and diffusive components of transport associated with the liquid water phase in the asphalt are expected to be quite low.

In most cases considered in this performance assessment, transport from the grout near the time of maximum impact is controlled by advection of and diffusion within the aqueous phase. However, water vapor diffusion is an additional phenomenon that can contribute to advective release from the grout vault. The pore solution of the grout has a high ionic strength because of the high concentration of salts in the waste to be grouted. This high ionic strength depresses the vapor pressure over the grout. The relative humidity in the pore space of the soil is expected to be very nearly 100%. Therefore, a driving force exists for water vapor to diffuse from the soil through the asphalt barrier and concrete vault to the grouted

waste. This mechanism provides a source of water at the grout surface independent of water infiltration from the land surface. It is incorporated within the model by placing a source of water in the cracks of a degraded structure to mimic the condensation of water vapor.

Degradation of the asphalt barrier will cause cracks to form and the asphalt mass to biodegrade. When cracking occurs, advection through the asphalt barrier will be dominated by advection of water through the cracks. The mechanisms that can lead to the development of cracks are described below. A forecast for potential cracking of the asphalt barrier is also provided. As a result of surface degradation attributed largely to biodegradation, the thickness of the intact barrier is gradually reduced and the effective diffusion coefficient increases with time.

3.3.5.1 Initial and Final States of the Asphalt Barrier

Flow and transport properties for the asphalt barrier are important to the analysis in this performance assessment. While intact, the asphalt barrier controls both the ionic diffusion and advective transport from the system. In addition, it serves as a barrier to water vapor diffusion. Model parameters for ionic diffusion and advective transport, as well as water-vapor diffusion, are described below.

Diffusion of radionuclides and chemical species through the asphalt barrier is an important process, because the diffusion coefficients in this media are the lowest of those throughout the engineered structure surrounding the grout. The diffusive and advective releases to the environment of mobile contaminants from the grout are controlled to low levels by the asphalt barrier while the barrier is intact. Advective releases become more significant as the hydraulic properties are changed over time by degradation.

The solid asphalt barrier consists of a mixture of asphalt and aggregate that is similar to a road pavement, except that the barrier is designed to contain less than 4% voids rather than ~10% as is typical for pavement. The mix contains 7.5 ± 0.5 wt% asphalt, which is approximately 16.2 vol% at the minimum asphalt content. The resulting barrier is a much higher quality product than common road pavement.

Literature Support for Asphalt Barrier Diffusivity. In selecting a diffusivity value for the barrier, literature values for the rate of diffusion through the individual components were used. This approach was taken because literature values for diffusion of salts in asphalt/aggregate mixtures are not available. Diffusion in asphalt has been reported by several investigators. Their articles are described below and summarized in Table 3.8.

Daiev and Vassilev (1985) measured the diffusion of strontium-90 into asphalt. In their experiments, strontium-90 was diffused into an asphalt layer for periods of 6 and 12 years. At the end of these time periods, the asphalt was cooled in liquid nitrogen and sliced into 30-micron layers. The thin asphalt

Table 3.8. Literature Values for Diffusion Through Asphalt

Source	Species	Diffusion Coefficient (cm ² /s)	Experimental Configuration
Daiev and Vassilev (1985)	Sr	3×10^{-12}	Tracer diffusion profile
Amarantos et al. (1985)	Na	1.1×10^{-11}	Leaching
Westsik et al. (1984)	Cs, Sr	1×10^{-13}	Leaching
Fitzgerald et al. (1970)	Na	7.1×10^{-11}	Leaching

layers were dissolved in benzene and the radioactivity counted. This technique produced profiles from which the diffusion coefficient was calculated. It varied from 1.2×10^{-12} to 3.0×10^{-12} cm²/s and was found to have a slight dependence on concentration.

Amarantos et al. (1985) studied the leaching behavior of nitrate salts immobilized in asphalt. The study included samples containing 20 to 60 wt% sodium nitrate immobilized in asphalt. The calculated diffusion coefficients of these samples ranged from 8×10^{-13} cm²/s to 1.1×10^{-11} cm²/s (for sodium leaching). It should be noted that in this type of leaching experiment, diffusion may not be the dominant release mechanism. This possibility is discussed in more detail below.

Westsik et al. (1984) performed leach tests on incinerator ashes immobilized in asphalt. The effective diffusion coefficient for cesium and strontium was approximately 1×10^{-13} cm²/s, measured with the ANS 16.1 procedure. Radioactivity up to 10^8 rads did not significantly affect the measured values.

Fitzgerald et al. (1970) investigated the immobilization of evaporator concentrate at Oak Ridge National Laboratory (ORNL) using asphalt. The asphalt samples were leached in water and diffusion coefficients were calculated. The effective diffusion coefficient for sodium was approximately 7.1×10^{-11} cm²/s.

Researchers at Brookhaven National Laboratory (Fuhrmann et al. 1989, Dougherty et al. 1986) performed numerous tests on asphalt with various loadings of anhydrous sodium tetraborate, including small amounts of cesium-137, strontium-90, and cobalt-60. Leaching in the presence of the sodium tetraborate could not be described by simple diffusion. The leaching progressed by hydrating salts and forming liquid pockets within the waste form. The pockets would then rupture, releasing the contaminant. This process was confirmed by photographing the surface with an electron microscope. The leach rates were very low for a period (1 year for 20% loading), and then accelerated. The rate of water diffusion into the sample was initially 5×10^{-11} cm²/s (determined using tritiated water) but as the sample swelled, the rate increased to 1.3×10^{-9} cm²/s.

There are several sources of uncertainty in the data described above for application to diffusion in the asphalt barrier. When waste is mixed into an asphalt waste form, the salt particles are not in solution. The salt concentration in the asphalt directly adjacent to a salt particle provides the driving force for diffusion. This concentration may be less than the bulk average concentration, depending on the waste loading. An analogous situation will exist in the asphalt barrier in that the salt concentration in the pore fluid of the concrete will be higher than the concentration in the asphalt. This uncertainty does not apply to the work done by Daiev and Vassilev (1985), because their data were based on actual salt concentrations in the asphalt.

As salts immobilized in asphalt begin to leach, the mechanism for release is not usually diffusion of contaminant through the asphalt. Instead, water vapor diffuses into the asphalt, forming saline inclusions and causing the asphalt to swell. When a saline inclusion ruptures, the contents are introduced into the leach solution. If this mechanism is dominating or contributing to release from the asphalt during the experiment, the calculated diffusivity of the contaminant in the asphalt is biased high.

In addition, the literature described above did not involve the asphalt material actually used in the grout vault construction and the reported studies were not conducted for the contaminants of interest in the grout performance assessment. Because of the uncertainties related to the literature information, experiments were conducted to support values adopted for the effective diffusion coefficient in the asphalt barrier.

Experimental Support for Asphalt Barrier Diffusivity. Two types of experiments were performed to quantify diffusion through the asphalt barrier. In the first experiment, asphalt (without aggregate) was placed in 1.3-cm- (0.51-in.-) deep x 3.2-cm- (1.3-in.-) square Teflon polytetrafluoroethylene (PTFE) molds. The molds were then immersed with one face of the asphalt exposed to a 4 molar NaNO_3 solution spiked with either $^{99}\text{TcO}_4^-$ or cesium-137. At selected times the sample was sectioned into 20-micron slices and analyzed. The diffusion coefficient was calculated from the profile of the contaminant concentrations within the asphalt. The values derived from the diffusion profile within the asphalt are shown in Table 3.9. The values in the table clearly support the value of $1 \times 10^{-10} \text{ cm}^2/\text{s}$ as a conservative estimate because all the measured diffusivities are lower. The values derived from the experiment are for pure asphalt. The incorporation of aggregate in the barrier should reduce the diffusion coefficient by a factor of 0.162 (volume fraction asphalt in barrier) to account for the smaller cross-sectional area available for diffusion.

In the second experiment, diffusion in the asphalt barrier was evaluated by leaching spiked cylinders of laboratory-prepared asphalt barrier material. The tracer was first dried onto the aggregate. The tracer samples contained one of these pairs: nitrate and iodine-125, nitrate and $^{99}\text{TcO}_4^-$, cesium-137, and $^{60}\text{Co}^{2+}$ -EDTA. The aggregate was coated with asphalt and compacted into a cylinder. The cylinder was leached to determine the effective diffusion coefficient. The results, summarized in Table 3.10, confirm that a value of $1 \times 10^{-10} \text{ cm}^2/\text{s}$ is a conservative diffusion coefficient for the asphalt barrier, and provide evidence that the aggregate does not act in some way to accelerate the release.

Table 3.9. Asphalt Diffusivity from Concentration Profile in Asphalt Following Immersion Test

<u>Contaminant</u>	<u>Diffusion Coefficient (cm²/s)</u>
¹³⁷ Cs ⁺	6.1 x 10 ⁻¹³
NO ₃ ⁻	5.1 x 10 ⁻¹³
⁹⁹ TcO ₄ ⁻	1.5 x 10 ⁻¹¹

Table 3.10. Effective Diffusion Coefficients from ANS 16.1 Leach Tests of Compacted Asphalt Barrier Material

<u>Contaminant</u>	<u>Diffusion Coefficient^(a) (cm²/s)</u>
¹²⁵ I ⁻	4.5 x 10 ⁻¹²
⁹⁹ TcO ₄ ⁻	2.3 x 10 ⁻¹¹
¹³⁷ Cs ⁺	<5 x 10 ⁻¹⁴
⁶⁰ Co ²⁺	8.3 x 10 ⁻¹²
EDTA	
NO ₃ ⁻	5.7 x 10 ⁻¹¹

- (a) Diffusion based on the concentration driving force calculated in the asphalt phase. Cumulative 330-day leach data. Samples not cured at elevated temperature. Samples cured at elevated temperature leached more slowly, presumably because the aggregate was more completely coated.

Initial Diffusion Properties of the Asphalt Barrier. Both the experimental results and the literature support a value of 1×10^{-10} cm²/s as a conservative estimate of diffusivity for all contaminants in the asphalt barrier. Use of this value is consistent with modeling diffusion as occurring in the asphalt phase, with no diffusion through the void space or mineral aggregate. Appendix K provides additional details of the work performed to support the ionic diffusivity selected. As with the concrete vault, no retardation of contaminants was assumed in the asphalt barrier.

Hydraulic Properties of the Intact and Biodegraded Asphalt Barrier. Asphalt is hydrophobic; it is not wetted by water. On the basis of this physical reality, it was assumed initially that for unsaturated environments the asphalt barrier was essentially impermeable. In order to reproduce this physical situation in the model of the asphalt barrier for the central sensitivity case (see Sections 3.6.1 and 3.6.5.1), the

barrier was assigned the properties shown in Table 3.11 for an initially impermeable material. The saturated moisture content was set to 16.2% volume to reflect the volumetric space associated with diffusive transport. However, the saturated hydraulic conductivity was set to 10^{-20} cm/s, essentially eliminating any actual water movement. Consequently, with respect to the hydraulics of the barrier, the assigned values for θ_s , θ_r , α and n do not influence the simulation and they were arbitrarily selected. Zones of the asphalt barrier identified as cracks were simply modeled as backfill soil.

Measured hydraulic properties of the asphalt material using water are not available. Because of the low affinity of water for asphalt and the very low hydraulic conductivity of this material, it is expected that transport of water through the intact barrier under unsaturated conditions will be a vapor diffusion phenomena rather than a liquid water phase phenomena. However, an estimate of water permeability was obtained from tests in which the nitrogen permeability was measured (Clemmer et al. 1992). In these tests, 15-cm- (5.9-in.-) diameter core samples of the field-placed barrier were sectioned into 10-cm (3.9-in.) samples and tested for nitrogen permeability. One side of the sample was pressurized with nitrogen to 50 torr (50-mm Hg, 0.97 psi) and then the change in pressure with time was measured to determine the permeability of the sample. These experiments indicate a nitrogen permeability of 1.1×10^{-11} cm/s. This value was adjusted based on viscosity to arrive at a saturated hydraulic conductivity of 2×10^{-13} cm/s for water. This value is considerably higher than the 1×10^{-20} cm/s value used for the asphalt barrier in the central sensitivity case. When the nitrogen permeability-based estimate of liquid water saturated hydraulic conductivity was known, it became the basis for selecting 1×10^{-11} cm/s as the initial K_s for the asphalt barrier in the central compliance case (see Section 3.6.2 and 3.6.3.1). Table 3.11 shows the van Genuchten-Mualem parameters for the initial, permeable model of the asphalt barrier. As implemented in the unsaturated zone numerical model, the van Genuchten-Mualem model is based on saturation (i.e., saturation = θ/θ_s), and the resulting saturation was simply sealed to the porosity assigned to the barrier material. Thus, the porosity of initially permeable and biodegraded asphalt materials differs from the materials' saturated moisture content.

After the asphalt is biodegraded, it is assumed that only the aggregate remains. The assumed particle-size distribution of the asphalt aggregate is similar to that of the backfill soil. Thus, the saturated hydraulic conductivity for completely degraded asphalt was assumed to be 3×10^{-2} cm/s (i.e., the value

Table 3.11. Hydraulic Properties for the van Genuchten-Mualem Model Applied to the Asphalt Barrier

Asphalt Barrier	Porosity	θ_s	θ_r	α (cm ⁻¹)	n	K_s (cm/s)
Initially Impermeable	0.162	0.162	0.0	1.0×10^{-7}	2.0	1×10^{-20}
Asphalt Cracks	0.371	0.371	0.045	0.0683	2.080	1×10^{-11}
Initially Permeable	0.04	0.371	0.045	0.0683	2.080	1×10^{-11}
Biodegraded	0.202	0.371	0.045	0.0683	2.080	3×10^{-2}

for backfill soil). The van Genuchten-Mualem parameters for a biodegraded asphalt barrier have been selected from those of backfill soil (see Table 3.11). However, the porosity was set to 20.2% volume, the total of asphalt and air-filled porosity in the asphalt barrier. The relative saturation predicted by the backfill soil water retention model was simply scaled to the total porosity of 0.202. The relatively high hydraulic conductivity of the aggregate that remains after biodegradation will support the transmission of significant amounts of water. Assigning modified backfill soil properties to the degraded asphalt material should support a smoother computational transition at the interface between asphalt and backfill soil.

Bottom Asphalt Barrier for Vaults 102-105. The asphalt barrier beneath the first four vaults (vaults 102-105) is composed of a 46-cm (18-in.) layer of asphalt barrier on top of a 46-cm layer of asphalt-coated gravel. On the top and sides of vaults 102-105, a barrier consisting only of asphalt barrier material has been installed. A 1-m-(3.3-ft)-thick asphalt barrier will completely surround future vaults.

In this effort to simulate the response of all 33 vaults, the layering of asphalt barrier and asphalt-coated gravel has been ignored for these 4 vaults. A 1-m (3.3-ft) asphalt barrier is modeled everywhere. The actual difference in transport behavior for the lower asphalt barrier for the first four vaults is expected to be small. The diffusivity of the asphalt-coated gravel barrier for ionic species was measured at $<2.5 \times 10^{-11} \text{ cm}^2/\text{s}$ (below detection limit), based on experimental measurements made with an electrical conductivity technique.^{(a)(b)} The experiments were performed with a centrifuge to control the water content at a desired value while measuring the electrical conductivity of the sample with a 1-kHz conductivity bridge. The electrical conductivity was then converted to a diffusivity using the Nernst-Einstein equation. The method was validated against half-cell measurements for soil from the grout site and against literature correlations used to predict soil diffusivity.^(c)

3.3.5.2 Water Vapor Diffusion

The phenomenon of water vapor diffusion is the primary reason for constructing the Grout Disposal Facility with an asphalt barrier instead of a porous media backfill. Water vapor diffuses with relative ease through a porous media barrier. However, the low-void asphalt barrier provides an excellent barrier to the diffusion of water vapor. In preliminary calculations, when the asphalt barrier was assumed to be impermeable, water vapor diffusion played a dominant role in release calculations because it provided the majority of the water contacting the waste. While the significance of water vapor diffusion has diminished in current release calculations because of the assignment of higher permeability and the resulting advective-dominated release, the phenomena still exists because of the high salt content of the wastes.

-
- (a) Conca, J. L. et al. *Experimental Determination of Diffusivity in A Gravel Cocoon*. December 1988. Pacific Northwest Laboratory.
 - (b) Wright, J. V. et al. *Experimental Detection of Diffusivity in Asphalt-Coated Gravel*. March 1988. Pacific Northwest Laboratory.
 - (c) Conca, J. L. et al. *Comparison of Diffusion Coefficient Measurement Techniques for Gravel Diffusion Coefficient Validation*. Draft Letter Report, August 1989. Pacific Northwest Laboratory.

Water vapor diffusion is not expected to lead to significant radionuclide releases (relative to dose limits in exposure scenarios) while the asphalt barrier is intact. Experimental measurements of water vapor diffusion through the asphalt barrier were made with laboratory-prepared specimens at different asphalt contents and samples compacted to different void contents. In addition, measurements were performed on core samples of the barrier taken from the vaults that are constructed. The details of the experimental measurements are described in Appendix L. The water vapor diffusivity is less than approximately $2 \times 10^{-5} \text{ cm}^2/\text{s}$ when the barrier material contains less than 4% voids and has at least 7.0 wt% asphalt, corresponding to the maximum void content and minimum asphalt content for barrier placement. The diffusivity decreased as the asphalt content increased or the void content decreased.

Water vapor diffusion becomes potentially significant if the asphalt barrier cracks as it degrades. The relative importance of water vapor diffusion is increased if advection through the grout is limited by a capillary break such as that provided by the gravel layer currently planned to be placed over the grout vault. The following paragraphs describe example calculations for water vapor diffusion. The first calculation is based on the assumption that the asphalt barrier is intact. The second calculation includes the effect of cracks on the barrier.

Intact Barrier. The grout vault was modeled to be isothermal at 17°C (62.6°F), indicating a time after the majority of cesium-137 has decayed and the grout has reached thermal equilibrium with the soil. While the vault is warmer than its surroundings, the gradient for water vapor diffusion is expected to be in the opposite direction or less than the gradient observed under isothermal conditions. Despite the arid climate and relatively low moisture contents in the soil column, the relative humidity in the soil surrounding the vault is expected to be nearly 100%. Measurements of relative humidity with thermocouple psychrometers have been made on grout samples obtained from a pilot-scale grout production test that used nonradioactive, simulated DSSF waste. An average of nine measurements indicated a relative humidity of 83%. This depression is assumed to exist at the inside of the asphalt barrier at the concrete vault's exterior. For this calculation, the concentrations of iodine-129, technetium-99, and salts causing the vapor pressure depression are assumed to be evenly distributed throughout the porosity of the grout, non-contaminated grout, and concrete, resulting in a relative humidity of 88%.

A rate of water vapor diffusion into the vault was calculated using the one-dimensional Fickian diffusion equation: rate equals product of cross section, diffusion coefficient, and concentration gradient. This water vapor was assumed to condense as pore fluid on the vault surface and combine with recharge moving through the unsaturated zone to the unconfined aquifer.

From the water vapor pressure at 17°C , 100% relative humidity in the soil, 88% relative humidity on the inside of the barrier, and an ideal gas assumption, the dC term was calculated as $1.74 \times 10^{-6} \text{ g/cm}^3$. The thickness of the barrier was assumed to be 3 ft (91.4 cm) and its surface area was $3 \times 10^7 \text{ cm}^2$. Using these values and a diffusion coefficient of $2 \times 10^{-5} \text{ cm}^2/\text{s}$ provided a mass diffusion rate of $1.14 \times 10^{-5} \text{ g/s}$ (0.36 L/yr) for each vault.

Cracks in Barrier. When the asphalt barrier is cracked, the cracks provide a more direct pathway for water vapor diffusion. The rate of water vapor transport in the cracks was estimated as shown above, based on the water vapor diffusivity in air and the area of the crack. With a cross sectional area of crack of 1 cm^2 , water vapor diffusivity in air of $0.24 \text{ cm}^2/\text{s}$, and a concentration change of $1.74 \times 10^{-6} \text{ g/cm}^3$ over the 91.4-cm- (3-ft-)thick barrier, the mass rate of water diffusion is $4.58 \times 10^{-9} \text{ g/s}$ (0.14442 g/yr) per each 1 cm^2 of crack.

This calculation is based on the assumption that the resistance of solute transport in the crack was negligible in both directions, toward the points of condensation and evaporation. In addition, the crack was assumed to be straight and clear of any debris. This assumption conflicts with that used for the numerical simulations where the cracks were assumed to have the pore structure of backfill soil. However, this assumption was used because assuming a crack filled with backfill soil represents a conservative approach for flow calculations where advection dominates, and assuming an empty crack represents a conservative approach for vapor diffusion calculations.

For a 37-m (length of the vault) crack, 1-cm wide, the area is $3,700 \text{ cm}^2$, resulting in the following water diffusion rate:

$$(4.58 \times 10^{-9} \text{ g/s cm}^2)(3700 \text{ cm}^2) = 1.69 \times 10^{-5} \text{ g/s (or 0.534 L/yr)} \quad (3.8)$$

This mass flow rate through such a crack is more than the amount of water diffusing through the entire intact barrier (0.36 L/yr). Thus, a 1-cm (0.39-in.) crack the length of the vault can potentially transmit more water than what diffuses through the rest of the intact barrier. Although the impact for this crack alone would not be significant, as cracks are postulated to become larger and more numerous over time, the potential exists for water vapor diffusion in the degraded barrier to be significant.

Water vapor diffusion from the soil to the grout was incorporated into some of the numerical simulations, particularly those for compliance cases (see Section 3.6.2.6). Water vapor diffusion was modeled as a source of water within the problem. In reality, the water condensing on the grout would originate from the soil column, however, no water is removed from the soil in the model to account for this. Such a treatment results in an increase in the amount of water in the soil column. The water vapor return rate is a fraction of the total recharge to the site.

Water Vapor Return in the Flow and Transport Model. The vapor returned to the high salt content waste is assumed to condense and form a liquid source of water in the space adjacent to the concrete or waste. When the asphalt barrier is intact, water vapor return has been shown to be small. Because diffusion through an array of cracks will be greater than through the intact barrier, water vapor

diffusion through the intact barrier was not evaluated. As the asphalt biodegrades, or as cracks form, the vapor is attracted to the exposed surface of the concrete and was assumed to be proportional to the areas of the exposed vault surface.

3.3.5.3 Degradation of the Asphalt Barrier

An asphalt barrier^(a) has been analyzed for the effects of degradation. However, the thick, high-quality asphalt planned for use in the vault asphalt barrier will not be exposed to all of the stress and degradation mechanisms to which the more commonly used forms of asphalt pavement are exposed. The dominant processes that degrade the much lower quality and thinner asphalt pavements are direct exposure to daily and seasonal cycles of hot and cold temperatures, sunlight, and traffic loads. Processes anticipated to contribute to asphalt barrier degradation are summarized in Table 3.12 and Appendix Q.

Table 3.12. Processes Anticipated to Cause Asphalt Barrier Degradation

Process or Mechanism	Associated Degradation
• Oxidation of asphalt	• Oxidation will begin at the surfaces of the asphalt barrier. The bulk of the asphalt in the barrier will oxidize over time. This mechanism will contribute to the brittleness of the barrier.
• Volatilization of asphalt	• Volatilization will probably happen early in the life of asphalt and will increase the asphalt's brittleness. The impact of volatilization on the flow or creep properties of asphalt will depend largely on the thermal environment the barrier experiences after placement, i.e., grout cure and radiolytic heating.
• Age hardening of asphalt	• Age hardening and polycondensation reactions affect the bulk properties of asphalt and will result in increased brittleness. This phenomena could have a significant impact on crack formation in the asphalt barrier. The rates tend to slow with time, but at some point can inhibit the crack healing processes because of the asphalt's decreasing ability to flow or creep.

(a) The design specification for the asphalt barrier calls for an asphalt content of $7.5 \pm 0.5\%$ by weight of the total asphalt mixture. Aggregate pretreated with an anti-stripping additive will therefore comprise $92.5 \pm 0.5\%$ by weight of the total. Placement specifications call for compaction to a minimum 96% of maximum density, and to less than 4% by volume of air void (Kaiser Engineers Hanford Company 1989).

Table 3.12. (contd)

Process or Mechanism	Associated Degradation
<ul style="list-style-type: none"> • Flow and creep of asphalt 	<ul style="list-style-type: none"> • Based on the above processes, one subjective estimate is that the barrier will tend to flow and creep for up to 100 years. However, flow and creep behavior is expected to constantly decrease. After 100 years, flow and creep will not occur.
<ul style="list-style-type: none"> • Thermal board disintegration 	<ul style="list-style-type: none"> • Cracks (5 mm; horizontal and vertical) in the wall-roof joint area caused by slumping of the asphalt barrier wall in response to thermal board disappearance.
<ul style="list-style-type: none"> • Short-term seismic stresses 	<ul style="list-style-type: none"> • No cracks; the probability of significant seismic loading is low in the near term and the asphalt is relatively ductile.
<ul style="list-style-type: none"> • Long-term seismic stresses 	<ul style="list-style-type: none"> • Cracks will be extended or initiated in the hardened or embrittled asphalt, accelerating hardening of the overall cross section of asphalt. Asphalt hardening should be a surface phenomena.
<ul style="list-style-type: none"> • Thermal stress 	<ul style="list-style-type: none"> • No cracks; thermal stresses are highest in the first 300 years and the asphalt should be relatively ductile, reducing the probability of thermal cracking.
<ul style="list-style-type: none"> • Construction joint weakness 	<ul style="list-style-type: none"> • No cracks; the surface preparations and the healing nature of fresh asphalt are expected to make this weakness insignificant. This expectation of cold joint strength was partially confirmed in tensile testing.
<ul style="list-style-type: none"> • Biodegradation 	<ul style="list-style-type: none"> • Biodegradation of exposed surfaces has been confirmed with a measured value for AR-6000 asphalt of 1.17×10^{-4} cm/yr (Luey and Li 1993) after 310 days in contact with wet (70% saturation) soil. It is postulated that the increased surface area exposed by cracks could accelerate biodegradation and result in an increased effective size of cracks. A rate of 1×10^{-4} cm/yr is a best estimate of actual long-term biodegradation in relatively dry soils. Biodegradation is a surface phenomena and it is anticipated that the rate of biodegradation will decrease over time. The barrier is not expected to disappear; rather, it should exist beyond 100,000 years.

The asphalt barrier will be buried in a dark and humid soil environment where biodegradation of exposed asphalt surfaces by microorganisms can occur. During the first 100 years following disposal, the asphalt barrier will be exposed to elevated temperatures caused by the heat generated as the grout cures and from the effects of radiolytic heat generated within the grout. The elevated temperatures may accelerate condensation reactions within the asphalt, cause the loss by volatilization of some low molecular weight organic compounds, and accelerate oxidation of the asphalt. The loss of volatiles will be limited by the thickness and permeability of the barrier. To escape the barrier, the low weight organics must diffuse to the surface of the asphalt barrier, the low weight organics must diffuse to the surface of the asphalt barrier. Because of the low permeability of the asphalt barrier, oxidation resulting from contact with air will be primarily a surface phenomenon. These processes increase the asphalt's viscosity, making the barrier more susceptible to cracking when exposed to seismic stresses over very long time periods (1,000 to 100,000 years). Eventually, the asphalt may become brittle and suffer significant cracking and biodegradation.

A preliminary analysis of the structural integrity of the asphalt barrier was completed.^(a) Structural properties of asphalt cores were measured and used to analyze the asphalt barrier under normal conditions and under a 0.25-G peak acceleration dynamic event. The analyses were for long-term (100 yr) linear creep and for a short-term seismic response. The analyses led to conclusions that neither creep of the fluid asphalt nor cracking of the barrier would be significant.

The conceptual model of asphalt degradation, divided into four periods (0 to 100, 100 to 10^3 , 10^3 to 10^4 , and 10^4 to 10^5 years), begins without any significant degradation in the first 100 years. During the second time period, cracks appear in the upper corners in response to degradation of the thermal insulation board; however, no additional cracks occur until the final period. As a result of embrittlement and recurring stresses related to seismic events, a pattern of 1-mm through-wall cracks on a 1-m (3.3-ft) grid appears during the 10^4 to 10^5 year period. It is unlikely that these patterned cracks would appear at one time or after only 10,000 years.

3.3.6 Permanent Isolation Barrier, RCRA Cover, Gravel Layer and Backfill Soil

Three components of the engineered disposal system lie between the land surface and the upper surface of the asphalt barrier: the permanent isolation barrier, RCRA cover, and gravel layer. Each is designed to limit or redirect infiltration from contacting and leaching the wastes. Between the isolation barrier and the RCRA cover lies a layer of soil. Similarly, between the RCRA cover and gravel layer lies a layer of filter sand.

(a) Kaiser Engineers Hanford Company. Draft, Issue D, May 1993. Diffusion Material Characterization Testing and Analysis Summary. Engineering Report B714ERI. Kaiser Engineers Hanford Company, Richland, Washington.

3.3.6.1 Permanent Isolation Barrier

Located at the soil-atmosphere boundary, the isolation barrier acts to recycle annual precipitation to the atmosphere by storing the precipitation in 2 m (6.6 ft) of silt-loam soil until the action of evapotranspiration can remove the water during the growing season. The details of this component of the engineered system (described in Section 2.7) are not modeled directly in the vadose zone simulation conducted here. Rather, the results of research on isolation barriers and recharge have been used to estimate a maximum average annual recharge that could occur through the protective barrier (design objective is 0.05 cm/yr). Gee et al. (1992) reported the results obtained on the 200 Area plateau at the Hanford Site from lysimeters containing silt loam. Lysimeters that were exposed to two times (2X) normal precipitation from 1987 through 1990 produced no drainage regardless of the presence or absence of plants. Unpublished data from continued monitoring of these lysimeters, which have since been exposed to three times (3X) normal precipitation, reveal no drainage from vegetated lysimeters but drainage through lysimeters maintained free of vegetation. A 0.1-cm/yr annual average recharge rate is selected based on the existing research; this rate is conservative with respect to both the reported research and the design objective of the isolation barrier program (see Section 2.1.7.4 and Appendix F).

The potential response of waste disposal systems to a greater recharge rate is of interest. Greater recharge could be a consequence of a variety of future events, e.g., climate change arising from changes in greenhouse gases or the onset of the next ice age, unforeseen degradation of the protective barrier system, or future agricultural land use resulting in irrigation on the Hanford Site and directly over the waste. The design life of the protective barrier system is 1,000 years; however, features such as the gravel admix included in the upper soil layer to prevent excessive wind erosion should enable the barrier to function indefinitely. Historically, the possible effects of greater recharge have been examined by analyzing system response to a uniformly applied 5-cm/yr recharge rate (U.S. DOE 1987, Appendices O, P, and Q). This performance assessment examines the potential impacts of greater recharge by simulating the effects of an increase of 5 cm/yr of recharge uniformly superimposed on present-day recharge for the entire Hanford Site. The potential impacts of irrigated agriculture on the unconfined aquifer will also be analyzed by applying incremental amounts of recharge on the present-day situation.

3.3.6.2 RCRA Cover

The RCRA cover is located between the base of the protective barrier and the upper surface of the asphalt barrier. Its purpose is to divert recharge away from the engineered structures containing waste. It is included in the engineered system to fulfill a RCRA requirement. The design requirement for saturated hydraulic conductivity of the RCRA cover is less than or equal to 1.0×10^{-7} cm/s (3 cm/yr). The barrier is composed of a mixture of two natural materials, fine soil and clay. The mixture, and its field placement, will be tested to assure compliance with the requirement for saturated hydraulic conductivity.

The cover has a design or service life of 30 years. However, it is composed of natural materials and in the vadose setting at the Hanford Site, it is expected to retain its unsaturated hydraulic properties and function as designed indefinitely. It will limit direct infiltration of recharge to its saturated hydraulic

conductivity, thus limiting water contact with the engineered system to a maximum of 3 cm/yr. In the nominal case of continuous 0.1-cm/yr recharge, a recharge rate well below the saturated hydraulic conductivity of 3cm/yr, virtually all of the recharge will move through the RCRA cover in an unsaturated state. However, in the high recharge case (≈ 5 cm/yr) where the isolation barrier is ineffective, the RCRA cover will limit direct recharge to 3 cm/yr and will redirect the additional infiltration to the right side of the modeled cross section (see Figures 2.31 and 3.2). Note the conclusion, that the 0.1-cm/yr recharge rate will be transmitted through the RCRA cover, is based primarily on simulations that use an arithmetic intermodal averaging scheme for hydraulic properties. The decision to use this scheme in simulations is based on analyses reported in Appendix H, Section H.5.4.

3.3.6.3 Gravel Layer

The gravel layer is placed immediately above the asphalt barrier and will be covered with a layer of filter sand. Because the sand is composed of fine soils (low air entry potential) and these same fines are absent from the gravel (high air entry potential), water infiltrating through the RCRA cover and sand will be routed to the right side of the engineered system in the sand (see the modeled cross section in Figure 3.2) rather than allowed to drain through the gravel layer.

3.3.6.4 Backfill Soil

The Grout Disposal Facility is constructed in an excavation. The vault and its surrounding engineered system is entirely buried when completed. Excavated soil is stored and later used to backfill around and above the engineered structure. Soil from the first excavation has been sampled and characterized for use in these simulations. The physical properties (e.g., particle size distributions) for backfill soil and filter sand are similar. In the absence of measured hydraulic properties for the filter soil, the hydraulic properties of backfill soil will be used for the filter sand.

3.3.6.5 Hydraulic Model Parameters for the Overlying Barriers

Of the overlying barriers described, the RCRA cover and gravel layer are simulated within the unsaturated zone profile. These are separated by filter sand and covered by backfill soil. As noted, the filter sand is assigned the hydraulic properties for this analysis because of the physical similarity in the two media.

The RCRA cover is composed of a mixture of fine soil and clay and must satisfy a design requirement for saturated hydraulic conductivity of 1.0×10^{-7} cm/s. Three samples were prepared and characterized in the laboratory.

Specifications call for the gravel to be washed and sieved before placement to remove fines and large rock. Thus, it is uniform and clean, and as a result its hydraulic characteristics in an unsaturated environment are distinctly different than those of a common gravel or soil. While such a gravel has a relatively high saturated hydraulic conductivity because of its open porosity, it acts as a barrier to water

flow in the unsaturated zone because of its relatively low unsaturated conductivity and its relatively high (near zero) air entry potential. Two gravel samples were characterized for unsaturated hydraulic properties, and only one for saturated hydraulic conductivity. The hydraulics of backfill soil were completely characterized for two samples. Laboratory data and methods for the characterization work, and methods of developing the hydraulic model parameters, are reported in Appendix J. The values of saturated hydraulic conductivity and of the van Genuchten-Mualem parameters are shown in Table 3.13. The soil characteristic curves are presented in Section 3.4.1.3 after material properties have been presented for all the media in the unsaturated profile.

3.3.6.6 Transport Model Parameters for the Overlying Barrier

Transport phenomena considered within materials of the overlying barriers were diffusion and sorption. Diffusion through unsaturated soils and sediments is provided below and applies to all media except gravel. A separate discussion of diffusion through gravel materials is provided. Sorption properties assigned to backfill soil are listed for the different transport groups.

Diffusion in Unsaturated Soils and Sediments. Water content is known to affect diffusion, and hence the effective diffusion coefficient, in unsaturated soils (Kemper and van Schaik 1966). The molecular diffusion coefficient for all species in pore water was assumed to be $2.5 \times 10^{-5} \text{ cm}^2/\text{s}$. In this analysis, the effective diffusion coefficients for the RCRA cover, backfill soil, and underlying natural sediments of the unsaturated profile were modified according to the empirical relationship published by Kemper and van Schaik (1966) (i.e., Eq. 3.4 in Section 3.2.5.2).

Data collected by Olsen, Kemper and van Schaik (1965) and Porter et al. (1960) for soils using sodium chloride as the diffusing species fit Equation 3.4 with "b = 10" and "a" being a function of soil surface area. The soils used in these studies ranged from sandy loam to clay soils, with the value for "a" ranging from 0.005 to 0.001, respectively (Olsen and Kemper 1968).

To be consistent with the measured data, values of "a" and "b" were selected as 0.005 and 10, respectively, for this performance assessment. These coefficients were measured for several Hanford soils using NaNO_3 in a half-cell diffusion experiment. The coefficients determined in the experiments gave comparable estimates of the effective diffusion coefficients in the soil at expected water contents.

Table 3.13. Hydraulic Properties for the RCRA Cover, Gravel Layer and Backfill Soil

Medium	θ_s	θ_r	$\alpha \text{ (cm}^{-1}\text{)}$	n	$K_s \text{ (cm/s)}$
RCRA Cover	0.448	0.0	5.39×10^{-4}	1.324	1.0×10^{-7}
Gravel Layer	0.5180	0.0140	3.5366	2.661	1.85
Backfill Soil	0.3710	0.0045	0.0683	2.080	0.03

Diffusion in Unsaturated Gravel. Diffusion in a gravel medium has been experimentally determined.^(a) Because of the low rate of diffusion in open gravel, traditional half-cell diffusion measurements were difficult and time consuming to perform. Therefore, an electrical conductivity technique similar to that used for measuring diffusivity of ions in water was developed and applied for measuring diffusivity in gravel.^(a) The technique showed good agreement with both the literature and the half-cell experiments for soils.^{(b)(c)} Measurements were obtained for a suite of four types of angular crushed gravel: 1) a river gravel composed of fractions of basalt, granite, gneiss, and quartzite; 2) a gravel composed entirely of basalt particles; 3) a gravel composed entirely of granitic particles; and 4) a gravel composed entirely of quartzite particles. Quartz gravel exhibited the lowest effective diffusion coefficients. The 4.0- to 6.3-mm quartz gravel had values ranging from $2.0 \times 10^{-10} \text{ cm}^2/\text{s}$ to $9.9 \times 10^{-10} \text{ cm}^2/\text{s}$ for volumetric water contents from 0.47% to 2.7%, respectively. Basalt gravel exhibited the higher values typical of basalt, granite, and river gravel. The effective diffusion coefficients for the 4.0- to 6.3-mm basalt gravel ranged from $3.8 \times 10^{-9} \text{ cm}^2/\text{s}$ to $1.3 \times 10^{-7} \text{ cm}^2/\text{s}$ for volumetric water contents from 0.81% to 5.1%, respectively. For the <2% volumetric water content expected to exist in the gravel layer, the effective diffusion coefficient of gravel is at most $1 \times 10^{-8} \text{ cm}^2/\text{s}$ for the gravel studied.^(d)

An asphalt coating was applied to gravel to determine the potential influence of a hydrophobic surface coating. Such a coating will lower diffusion through gravel by preventing the formation of continuous water films on the gravel particles.^(e) Measurements of the effective diffusion coefficient in asphalt-coated gravel were consistently below the detection limit of $2.5 \times 10^{-11} \text{ cm}^2/\text{s}$. The gravel samples used in the tests were initially saturated and then allowed to gravity drain prior to the measurement, so the water content represents a worst-case condition.

The effective diffusion coefficient used for the gravel layer in these analyses was $2.5 \times 10^{-10} \text{ cm}^2/\text{s}$. No correction was made for the volumetric moisture content because experiments were conducted at

-
- (a) Conca, J.L., J.V. Wright, D.L. Lane, R.C. Britton, J.S. Allen, K.H. Pool, and N.H. Uziemblo. December 1988. *Experimental Determination of Diffusivity in a Gravel Cocoon*. Letter Report to Westinghouse Hanford Company from Pacific Northwest Laboratory, Richland, Washington.
 - (b) Conca, J.L., J.V. Wright, and D.A. Lamar. August 1989. *Comparison of Diffusion Coefficient Measurement Techniques for Gravel Diffusion Coefficient Validation*. Letter Report to Westinghouse Hanford Company from Pacific Northwest Laboratory, Richland, Washington.
 - (c) Lamar, D.A. April 1989. *Measurement of Nitrate Diffusivity in Hanford Sediments via the Half-Cell Method*. Letter report to Westinghouse Hanford Company from Pacific Northwest Laboratory, Richland, Washington.
 - (d) Conca, J.L., J.V. Wright, D.L. Lane, R.C. Britton, J.S. Allen, K.H. Pool, and N.H. Uziemblo. December 1988. *Experimental Determination of Diffusivity in a Gravel Cocoon*. Letter Report to Westinghouse Hanford Company from Pacific Northwest Laboratory, Richland, Washington.
 - (e) Wright, J.V., G.A. Whyatt, E.G. Baker, and D.H. Mitchell. February 1989. *Experimental Determination of Diffusivity in Asphalt-Coated Gravel*. Letter report to Westinghouse Hanford Company from Pacific Northwest Laboratory, Richland, Washington.

moisture contents anticipated to exist in the gravel layer. The value employed is typical of quartz gravel and is below measured values for commonly available angular crushed gravel composed of basalt, granite, or river source materials.

The effective diffusion parameters used to model diffusive transport in the engineered materials and soils/sediments are listed in Table 3.14. Values for the Hanford and Ringold formations are also shown. Note that the effective diffusion coefficient applied for grout in the central sensitivity case was $1 \times 10^{-6} \text{ cm}^2/\text{s}$ instead of the experimentally determined value of $0.578 \times 10^{-6} \text{ cm}^2/\text{s}$. The value used in the simulation was higher than the measured value, and therefore conservative in terms of the measured value.

Sorption in Backfill Soil. Sorption was considered only in the grout (see Section 3.3.3.1 and Table 3.3) and the natural sediments of the unsaturated zone. To be conservative, sorption has been neglected in the RCRA cover, gravel layer, asphalt barrier, and concrete vault. It is included within the backfill soil since this soil is a simple mixture of the upper portion of the natural sediment profile created when excavating for vault construction. The code used to simulate contaminant transport in the unsaturated zone requires the following data to calculate sorption (i.e., retardation factor, or R): distribution coefficient (R_d), grain or particle density, and total porosity. Values for each parameter are given in Table 3.15. Because R_d data do not exist for the spectrum of soils and contaminants in the unsaturated zone profile, single conservative values of R_d have been adopted to represent the range of contaminants in each transport group.

Table 3.14. Effective Diffusion Coefficient Parameters for Modeling Diffusive Transport in Unsaturated Soils and Engineered Materials

Material	$D_{ab} \text{ (cm}^2/\text{s)}$	a	b
RCRA cover	2.5×10^{-5}	0.005	10
Backfill soil	2.5×10^{-5}	0.005	10
Gravel layer	2.5×10^{-10}	1	0
Asphalt Barrier $t < 90,000 \text{ yr}$	1×10^{-10}	1	0
Asphalt Barrier $t > 90,000 \text{ yr}$	2.5×10^{-5}	0.005	10
Asphalt cracks	2.5×10^{-5}	0.005	10
Concrete vault	5×10^{-8}	1	0
Concrete cracks	2.5×10^{-5}	0.005	10
Grout	1×10^{-6}	1	0
Hanford, sand	2.5×10^{-5}	0.005	10
Hanford, gravel	2.5×10^{-5}	0.005	10
Ringold	2.5×10^{-5}	0.005	10

Table 3.15. Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments

Transport Group	Species	Grout $R_d^{(a)}$ (ml/g)	Soil $R_d^{(b)}$ (ml/g)
1A	^3H , ^{103}Ru , $^{106}\text{RuRh}$, ^{125}Sb , ^{129}I	0	0
2A	^{99}Tc	2	0
2B	^{94}Nb , ^{95}Nb	2	0.67
3A	Selected chemicals only	125	0
3C	^{60}Co , ^{63}Ni , ^{79}Se , ^{90}Sr , ^{113}Sn , ^{126}Sn , ^{134}Cs , ^{135}Cs , ^{137}Cs , ^{226}Ra , ^{237}Np	125	3
4A	^{14}C , ^{234}U , ^{235}U , ^{238}U	2,625	0
4D	^{95}Zr , $^{144}\text{CePr}$, ^{152}Eu , ^{154}Eu , ^{155}Eu , ^{230}Th , ^{238}Pu , $^{239/240}\text{Pu}$, ^{241}Pu , ^{242}Pu , ^{241}Am , ^{243}Cm , ^{244}Cm	2,625	21

- (a) The retardation factor, R , is calculated from the distribution coefficient, R_d . The relationship is $R = 1 + (\rho_b R_d / \theta)$. For grout the additional data are as follows: particle density = 2.62 g/ml, $\theta = 0.5781$, bulk density = particle density $\times (1 - \theta)$.
- (b) The additional data for soils are as follows: All particle densities, $\rho_b = 2.72$ g/ml; backfill soil, $\theta = 0.371$; Hanford formation sandy sequence, $\theta = 0.4203$; Hanford formation gravel sequence, $\theta = 0.3584$; Ringold formation, $\theta = 0.4982$.

Presently, the available data base for contaminant adsorption onto Hanford soils includes laboratory-derived R_d values for Co, Sr, Np, Pu, Am, Cs, Ru, and Sb for high-level tank waste solutions (Knoll 1966, 1969; Delegard and Barney 1983); Sr, Zr, Tc, Ru, I, Cs, Ce, Eu, Co, Np, Pu, Am, and Cm for selected sediments and solutions similar to diluted Hanford wastes and groundwaters (Ames and Rai 1978; Benson 1960; Serne and Rai 1976; Sheppard, Kittrick, and Hardt 1976; Hajek 1966; Routson and Serne 1972; Serne, Routson, and Cochran 1973; Routson, Jansen, and Robinson 1976; Routson, Barney, and Seil 1978; Routson, Barney, and Smith 1980; Routson et al. 1981; Gee et al. 1981); and Mn, Co, Sr, Cs, Tc and I, for grout leachates contacting a typical 200 East Area sediment (Serne et al. 1987). Currently available geochemical data for release and retardation involving Hanford wastes and sediments are presented in Serne and Wood (1990). For many other elements, R_d values can be estimated by analogy to other similar elements. For the mobile species of greatest concern (^{99}Tc , ^{129}I , NO_2 , and NO_3), no sorption ($R_d = 0$) was included in the soils or sediments.

3.4 Unsaturated Sediment and Unconfined Aquifer Pathway

Analyses of flow paths through the unsaturated sediments between the grout vaults and the water table, and the flow paths in the unconfined aquifer, require definition of units and the hydraulic and

transport characteristics. The unsaturated sediment pathway includes the backfill soil around the engineered disposal facility and the undisturbed Hanford and Ringold formations. The characteristics of backfill soil were presented in the section on the engineered system (Section 3.3.6). The unconfined aquifer pathway includes consideration of groundwater flow through the Hanford and Ringold formations.

This section describes the conceptual models and data for the central sensitivity case. Many of the parameters were varied in the design and sensitivity cases as well as the compliance cases discussed later in Section 3.6. In Chapter 2, the general Hanford Site stratigraphy was established. The stratigraphy at the Grout Disposal Facility and in the unconfined aquifer model is described in this section. In all of the hydrogeologic conceptualizations, a porous media model is used, with homogeneous and isotropic properties assigned to computational cells or blocks. Additional detail on the conceptualization, geologic stratigraphy, and physical and hydraulic properties of sediments at the Grout Disposal Facility is provided in Appendix J.

3.4.1 Water Flow in Unsaturated Sediments

Predicting water flow in the unsaturated sediments surrounding and below the grout vaults requires specification of geologic stratigraphy, the saturated hydraulic conductivity, and unsaturated hydraulic characteristics, including porosity and parameters describing the unsaturated moisture retention characteristics. In the numerical flow and transport models, the hydraulic properties of porous media are represented by mathematical functions. For this performance assessment, the van Genuchten and Mualem hydraulic conductivity functions were selected. The van Genuchten relationship has been applied to a variety of soils at different sites and is appropriate for sediments beneath the Grout Disposal Facility. The Mualem hydraulic conductivity function was necessary because unsaturated hydraulic conductivities are difficult to measure in the laboratory.

3.4.1.1 Stratigraphic Layering

The geologic descriptions of the different layers were derived from visual examination by geologists in the field. Particle size distributions were determined by sieving in the laboratory. Generally, samples were sieved to remove particles >2 mm in diameter before further testing was conducted. Particles >2 mm are categorized as gravel. The distribution of particle sizes <2 mm is used to classify sediments into textural categories such as clay or sand. Two procedures were used to determine the particle size distributions of sediments analyzed for the grout performance assessment. The two procedures are described in American Society for Testing and Materials (ASTM) (1985) and Gee and Bauder (1986). Approximately 50 g of material that passed a 2-mm sieve was used with the hydrometer method and wet sieving to determine the particle size distribution over the full range of sizes <2 mm.

Geologic logs and sediment sample analyses from available wells at the Grout Disposal Facility were reviewed to identify the dominant sedimentary features. Figure 2.1 in Appendix J shows the locations of these wells and sediment samples relative to the Grout Disposal Facility. The general geologic

stratigraphy at the Grout Disposal Facility is shown in Figure 3.11. The stratigraphy depicted in this figure consists of alternating layers of silt, sand, and gravel in a dune sand unit, the Hanford formation, and the Ringold formation. Underlying the Ringold Formation is the Elephant Mountain Member of the Columbia River basalts. The saturated hydraulic conductivity of this basalt is much lower than that for the overlying sediments; the basalt was therefore considered to be impermeable and to constitute the base of the geologic profile. As indicated in Figure 3.11, the Hanford formation consists of layers that are predominantly sand and layers that are predominantly gravel. The Ringold formation consists predominantly of a sandy gravel.

The sandy sequence of the Hanford formation is a coarse-to-fine-grained sand unit that averages 60-m thick in the 200 East Area. The characteristics of the sandy sequence of the Hanford formation were generated from 28 samples from well 299-E25-234, 5 samples from the 241 AP Tank Farm excavation, 21 samples from pits at the U.S. Ecology site, 3 samples from the 200-BP-1 site, and 3 measurements from the bottom of the existing grout pit (Dames and Moore 1988). These data were used to characterize the sandy sequence.

The lower gravel sequence of the Hanford formation is a pebbly, very coarse sand-to-sandy gravel, about 10-m thick at the Grout Disposal Facility. It overlies the Ringold Formation. Characteristics of this unit were derived from two samples obtained from well 299-E-25-234, eight samples from the 200-BP-1 site, two samples from B Pond, and two samples from pits at the U.S. Ecology Site. Some of the samples were from the upper gravel sequence of the Hanford formation, which is absent in the vicinity of the Grout Disposal Facility. The upper and lower gravel sequences of the Hanford formation are textually similar and are more or less indistinguishable from each other except for stratigraphic position (Connelly et al. 1992a, b).

The Ringold formation averages 30-m thick at the Grout Disposal Facility, consisting of well-rounded pebble-to-cobble-size gravel with a matrix of sand, silt, and some clay. The Ringold formation is variably consolidated, ranging from a well-cemented conglomerate to open-work uncemented gravel. The characteristics of the Ringold formation at the Grout Disposal Facility were derived from four samples from B Pond and one sample from the U.S. Ecology Site. No samples of the Ringold formation beneath the Grout Disposal Facility were available.

The characteristics of the backfill soil and gravel are included here because of their importance in the stratigraphic profile; i.e., soil will be used to backfill around the grout vaults and gravel will be used to form a sloped capillary barrier above the vaults. The characteristics of backfill soil were determined from a sample taken from a stockpile of sand excavated during construction of the GDF pit. The sample was sieved so that only the <2-mm size fraction was used to determine hydraulic properties. The resulting particle-size distribution was 91% sand, 3% silt, and 6% clay.

Figure 3.11. Sediment Stratigraphy in the Vicinity of the Grout Site

3.4.1.2 Saturated Hydraulic Conductivity

Saturated hydraulic conductivities for unsaturated sediments beneath the grout vaults were determined with laboratory measurements. These laboratory measurements are based on application of the Darcy flow equation to a sample of uniform cross-sectional area. Two different methods were used. For the majority of materials, a falling-head permeameter method was used. For high permeability materials such as the coarse sands and gravels, a constant-head permeameter method was used. The details of these methods and the apparatus used for each are provided in Appendix J.

From the geologic information used to generate the stratigraphy shown in Figure 3.11, and from a summary of the hydrogeology of the 200 East Area by Cushing (1991), gravel was observed to be present in unsaturated sediments beneath the grout facility. Except for samples collected above the 126-ft (38.4-m) depth in well 299-E25-234, all hydraulic conductivity measurements were made on the <2-mm-diameter particle-size fraction. As documented in Appendix J, a method proposed by Bouwer and Rice (1983) was used to estimate the bulk hydraulic properties of a mixture containing sand and gravel from the hydraulic properties of the sand and volume fraction of the gravel.

Results of the saturated hydraulic conductivity measurements are presented as averages. The averages of the saturated hydraulic conductivities were calculated as geometric means because saturated hydraulic conductivity has often been shown to be lognormally distributed (Hills and Wierenga 1991; Sudicky 1986).

Saturated hydraulic conductivity measurements for the sandy sequence of the Hanford formation were reported by Smoot et al. (1989; 33 samples) and Connelly et al. (1992b; 27 samples). These data included 28 measurements from well 299-E-25-234, 5 measurements from the 241-AP Tank Farm, 21 measurements from U.S. Ecology, 3 measurements from the 200-BP-1 site, and 3 measurements of in situ saturated hydraulic conductivity made with a borehole permeameter at the bottom of the existing grout pit (Dames and Moore 1988). Equations 4.3 and 4.4 in Appendix J were used to scale the hydraulic properties of the first 4 samples from the 241-AP Tank Farm for gravel content (Smoot et al. 1989). Somewhat fewer data were available for the lower gravel sequence of the Hanford formation. Saturated hydraulic conductivity data were reported by Smoot et al. (1989; 2 samples) and Connelly et al. (1992b; 12 samples). These data include two measurements from well 299-E25-234, eight measurements from the 200-BP-1 site, two measurements from B Pond, and two measurements from the U.S. Ecology Site. Corrections for gravel content were not performed for the lower gravel sequence of the Hanford formation.

Saturated hydraulic conductivity measurements for the Ringold formation were reported by Connelly et al. (1992b; five samples). These data consisted of four measurements from near B Pond and one measurement at the U.S. Ecology Site. These measurements were not corrected for gravel content.

3.4.1.3 Unsaturated Hydraulic Characteristics

The flow of water and contaminant transport in an unsaturated porous medium is governed by the relationships among water content, matric potential or pressure head, and hydraulic conductivity. Within the numerical model used in this performance assessment, these relationships are represented by mathematical functions containing one or more fitted parameters. A water retention function is used to describe the relationship between water content and matric potential. The water retention function used to represent soils and engineered materials for this performance assessment was proposed by van Genuchten (1980) and is listed in Appendix J (Equation 4.1). An unsaturated hydraulic conductivity function is used to describe the relationship between unsaturated hydraulic conductivity and matric potential. Because unsaturated hydraulic conductivity is difficult to measure directly, it is often calculated. The predictive model of Mualem (1976) was used to calculate the unsaturated hydraulic conductivity function, and the unsaturated hydraulic conductivity function of van Genuchten (1980) was used to represent the hydraulic conductivity data as described in Appendix J (Equation 4.2).

Total porosity, the measure of relative volume of pores capable of filling with water, was determined from measurements of particle and bulk densities, according to an equation by Hillel (1982) described in Appendix J. Particle density was determined with a pycnometer method (Blake and Hartge 1986a; Appendix J). Bulk densities of sediments were determined with the method outlined by Blake and Hartge (1986b; Appendix J).

Four different methods were used to determine water retention data over the full range of matric potentials from full saturation to residual (irreducible) saturation. This was necessary because each of the different methods is accurate within a certain range of saturations and pressures and not accurate outside of that range. The methods used (described in detail in Appendix J) were 1) the hanging water column method (Klute 1986), 2) a column method, and 3) the pressure-plate extraction method. In all cases, measurements were conducted on draining samples. No measurements were made as samples were wetted, which would have documented the extent of hysteresis. Hysteresis was not included in the numerical models employed in the performance assessment.

Where possible, undisturbed samples were obtained to preserve the in situ structure of the materials being measured. Most of the samples, however, were disturbed because of sampling methods such as drilling. The disturbed samples were packed to known densities before measurements were made.

The numbers of samples for the different layers (Hanford formation sand and gravel sequences, and the Ringold formation) are the same as for the hydraulic conductivity data indicated in the previous section. Measurements of water content were made as a function of saturation. The water retention parameters θ_s , θ_r , α , and n from the van Genuchten (1980) function were fit to the measured water retention data using a nonlinear, least-squares, curve-fitting program developed by Yates et al. (1992). Generally, water retention data from the various measurement methods were combined and used for fitting the parameters in the van Genuchten water retention function. When data from pressure plate and hanging water column methods overlapped, the overlapping pressure plate data were omitted during curve fitting.

because they were considered less reliable. Water retention data from duplicate samples were refit. Therefore, parameter estimates in Appendix J from well 299-E-25-234 vary from those reported in Smoot et al. (1989) and Connelly et al. (1992b).

The average parameters for sediments from the Hanford and Ringold formations and for other materials comprising the engineered Grout Disposal Facility are listed in Table 3.16. For parameters other than saturated hydraulic conductivity (K_s) listed in the table, arithmetic mean values were used to compute averages. Figures 3.12 and 3.13 illustrate the water retention and unsaturated hydraulic conductivity relationships, respectively, for the materials listed in Table 3.16.

3.4.2 Sorption

For the transport of some contaminants from the grout waste form, distribution coefficients (R_d) were used to describe sorption of some contaminants. The R_d is a function of retardation methods of chemical precipitation/dissolution of bulk and solid phases, chemical substitution of one element for another in a solid phase, exchange of the stable isotope of an element with a radioactive isotope in solution, cation and anion exchange, and adsorption (Muller, Langmuir and Duda 1983). These mechanisms are described by a single empirical R_d . Separate retardation factors (R) were used for the grout and sediments, but values were constant in each region of the model domain.

Table 3.16. Hydraulic Properties for Engineered Materials and Unsaturated Sediments

Material	θ_s	θ_r	α (cm-1)	n	K_s (cm/s)
Hanford formation					
Sandy sequence	0.4203	0.0234	0.1943	1.868	1.55×10^{-3}
Lower gravels	0.3584	0.0213	0.0290	1.613	2.73×10^{-4}
Ringold formation	0.4982	0.0283	0.0176	1.338	2.42×10^{-6}
Backfill soil	0.3710	0.0450	0.0683	2.080	3.00×10^{-2}
Gravel	0.5180	0.0140	3.5366	2.661	1.85
Grout/Cold Cap	0.5781	0.000	1.08×10^{-5}	1.650	1.47×10^{-8}
Concrete	0.2258	0.000	7.6×10^{-6}	1.393	3.75×10^{-10}
Asphalt Barrier	0.162	0.000	1.0×10^{-7}	2.000	1.0×10^{-20}
RCRA Cover	0.448	0.000	5.39×10^{-4}	1.324	1.0×10^{-7}

Figure 3.12. Water Retention Characteristics for Engineered Materials and Unsaturated Sediments

Figure 3.13. Unsaturated Hydraulic Conductivity Relationships for Engineered Materials and Unsaturated Sediments

In all of the simulations, sorption of contaminants in the concrete and asphalt barriers was assumed to be zero. This assumption was made to be conservative in estimating the release of contaminants from the engineered Grout Disposal Facility. The R_d for the different transport groupings for grout, concrete and asphalt barriers, and unsaturated sediments are listed in Table 3.17. In the simulations performed, the Hanford and Ringold formations employ the same R_d as the backfill soil. The specification of sorption properties also requires the grain or particle density of materials, taken to be 2.72 g/cm^3 for all sediments. Sorption also varies with water content in unsaturated sediments. To be conservative, total porosity was used rather than water content for each sediment type.

Table 3.17. Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments

Group	Species	Grout R_d (ml/g)	Grout $R^{(a)}$ (-)	Soil $R_d^{(b)}$ (ml/g)
1A	^3H , ^{103}Ru , $^{106}\text{RuRh}$, ^{125}Sb , ^{129}I	0	1	0
2A	^{99}Tc	2	4.82	0
2B	^{94}Nb , ^{95}Nb	2	4.82	0.67
3A	Selected chemicals only	125	240	0
3C	^{60}Co , ^{63}Ni , ^{79}Se , ^{90}Sr , ^{113}Sn , ^{126}Sn , ^{134}Cs , ^{135}Cs , ^{137}Cs , ^{226}Ra , ^{237}Np	125	240	3
4A	^{14}C , ^{234}U , ^{235}U , ^{238}U	2625	5020	0
4D	^{95}Zr , $^{144}\text{CePr}$, ^{152}Eu , ^{154}Eu , ^{155}Eu , ^{230}Th , ^{238}Pu , $^{239/240}\text{Pu}$, ^{241}Pu , ^{242}Pu , ^{241}Am , ^{243}Cm , ^{244}Cm	2625	5020	21

(a) $R = 1 + (\rho_b R_d / \theta)$; data required to make this calculation are as follows:

Grout: Particle density = 2.62 g/ml , $\theta = 0.5781$, Bulk density (ρ_b) = Particle density $\times (1 - \theta)$

Backfill Soil 2.72 0.371

Hanford - Sandy 2.72 0.4203

Hanford - Gravel 2.72 0.3584

Ringold 2.72 0.4982

(b) No sorption in asphalt barrier, concrete vault, cracks in either asphalt or concrete, RCRA cover, or gravel.

3.4.3 Boundary and Initial Conditions for the Unsaturated Sediments

Boundary conditions for water flow in the model domain are summarized in Table 3.18. The basis for 0.1-cm/yr recharge at the upper boundary was established in Section 2.1.7.4. The 0.1-cm/yr recharge rate is based on current climatic conditions and the presence of a silt loam soil on top of the multilayered (Hanford) protective barrier with shallow-rooted vegetation. To include consideration of an ineffective barrier in this performance assessment, a higher recharge rate of 5 cm/yr was evaluated as a sensitivity case. The side boundaries are assumed to be no-flow by symmetry between grout vaults. The lower boundary is prescribed pressure, which allows a flux of water across the boundary to the water table.

Transport boundaries are also summarized in Table 3.18. Specification of zero concentration at the upper boundary results in a no-flux boundary condition--i.e., no contaminant flux is allowed across the upper boundary. The zero concentration gradient condition along the side and lower boundaries results in contaminant flux at the concentration reaching the boundary. Thus, contaminants are advected, but not diffused, across the side and lower boundaries. Because water flow is predominantly downward in the model domain, most of the contaminant flux occurs across the lower boundary.

Upward diffusion of contaminants was included as a case in this performance assessment to determine if contamination of soil above the grout vault could be important. Evaluation of this case required a zero recharge rate. Even the limited recharge of 0.1 cm/yr results in downward advection of contaminants. All properties were the same as those listed above, except the recharge rate at the upper boundary and concentration gradient was set to zero. The concentration at the bottom boundary was set to zero for this case as well. The top boundary condition prevents contaminants from diffusing out of the top of the system. For the purpose of evaluating dose, the protective barrier was not included and radionuclide concentrations in backfill soil at the top of the profile were used in an individual garden scenario. If the protective barrier were included, additional attenuation of contaminants would occur.

Table 3.18. Boundary Conditions for the Flow and Transport Analyses of Grout Performance

Boundary	Condition
Flow Analysis	
Upper boundary	Constant recharge rate 0.1 cm/yr (5 cm/yr included as a sensitivity case)
Right/left boundaries	No flow by symmetry, total potential gradient = 0.0
Lower boundary	Water table at atmospheric pressure
Transport Analysis	
Upper boundary	Concentration = 0.0
Left/right boundaries	Concentration gradient = 0.0
Lower boundary	Concentration gradient = 0.0

Initial hydraulic conditions in the soils underlying the Grout Disposal Facility were assumed to be related to the long-term recharge rate of 0.1 cm/yr. Based on soil hydraulic properties, the unit hydraulic gradient theory was applied to determine the initial moisture content and matric potential for the various stratigraphic units in equilibrium with 0.1-cm/yr recharge. Table 3.19 is a summary of the initial conditions used for soils and engineered materials in the model domain depicted in Figure 3.2.

Initial contaminant concentrations in the model domain were as follows for all contaminants:

Contaminated grout monolith $C(x,t = 0) = 1.0$

Backfill soil, noncontaminated grout, engineered structures, and underlying sediments $C(x,t = 0) = 0.0$

Thus, the contaminated grout monolith contained all of the inventory at the time simulations began. Actual concentrations of specific radionuclides and hazardous chemicals were derived by considering the inventories of each contaminant.

3.4.4 Water Flow in the Unconfined Aquifer

The uppermost aquifer at the Hanford Site is the unconfined aquifer. Because of its shallow depth compared to underlying confined aquifers, the unconfined aquifer will be most accessible to the public under possible future site uses. Therefore, the unconfined aquifer was evaluated in several cases for this performance assessment. One case consisted of evaluating impacts from transport of contaminants to a hypothetical well 100-m downgradient from the Grout Disposal Facility. The second case consisted of evaluating transport and discharge of contaminants to the Columbia River and downstream transport to locations where exposures occur.

Table 3.19. Summary of Initial Conditions for Analysis of Flow in the Central Sensitivity Case

Material	Moisture Content	Saturation	Matric Potential (cm)
Backfill soil	0.056	0.151	338
RCRA barrier/clay	0.446	0.996	338
Concrete	0.226	1.000	338
Gravel	0.014	0.027	338
Asphalt	0.162	1.000	338
Grout	0.578	1.000	338
Hanford formation, sands	0.059	0.140	83
Hanford formation, gravels	0.087	0.242	496
Ringold formation	0.320	0.642	206

3.4.4.1 Conceptual Model and Data for the Unconfined Aquifer

The unconfined aquifer is comprised of sediments in both the Hanford and Ringold formations. The base of the unconfined aquifer is the top of basalt or top of the lower Ringold formation (clay), if present (Newcomb, Strand, and Frank 1972). The stratigraphy of the unconfined aquifer used in this performance assessment is based on previous studies of the Hanford Site--for the 200 West Area, Lindsey et al. (1991); the 200 East Area, Lindsey et al. (1992); the 100 Areas, Lindsey (1992); and the Hanford Site as a whole, Brockhaus (1989).

The unconfined aquifer at the Hanford Site is bounded by the Yakima and Columbia rivers. Other portions of the aquifer are bounded by the basalt outcrops of Rattlesnake Mountain and Umtanum Ridge and by Cold Creek and Dry Creek valleys. Interior boundaries consist of Gable Butte and Gable Mountain. The Yakima and Columbia River boundaries are treated as prescribed head. The elevations of the Yakima River represented on a U.S. Geological Survey map were used to determine the prescribed heads. The average elevations of the Columbia River during June 1984 were used to prescribe head along the Columbia River boundary. Rattlesnake Mountain, Gable Butte, and Gable Mountain are assumed to be no-flow boundaries. The prescribed flux for Cold Creek and Dry Creek valleys was assumed to be 321,945 ft³/d and 47,014 ft³/d, respectively, as documented in Jacobson and Freshley (1990).

The unconfined aquifer is impacted by both natural and artificial recharge distributed over the Hanford Site. Natural recharge results from precipitation in excess of evapotranspiration and varies over the Site in response to differences in soil type and vegetation patterns. The distribution of natural recharge documented by Jacobson and Freshley (1990) was used for unconfined aquifer modeling in this performance assessment. Artificial recharge from site operations has a significant effect on the unconfined aquifer. Although applications of the unconfined aquifer model do not include artificial recharge, it was included for model calibration to current conditions.

A series of inhomogeneity zones were used in the SLAEMS code (SLAEMS and other codes used in the grout performance assessment are described in Section 3.5) to represent heterogeneity of the system. The zones contained multiple layers of varying thickness and hydraulic conductivity (Figure 3.14).

3.4.4.2 Calibration of the Unconfined Aquifer Model

Calibration of the SLAEMS model involves adjusting the aquifer parameters (e.g., location of geologic units) and material properties (e.g., saturated hydraulic conductivities) to match known field conditions with the values computed by the model. Using the previously described boundary conditions and average artificial recharge during 1984, and adjusting the inhomogeneity zones, improved the agreement between the model-predicted heads and the known well water levels. Zones of low hydraulic conductivity were employed to model the groundwater mounds that exist under the 200 West and 200 East areas as a result of artificial recharge. High conductivity zones were introduced or enlarged to model sandy areas. In a stepwise process the hydraulic conductivities used in the model were then refined to find the best match for the domain of interest (the area underlying the Grout Disposal Facility and alternate pathways

Figure 3.14. Calibrated Hydraulic Conductivity Distribution for Inhomogeneity Zones

to the river). The final hydraulic conductivities used for the Hanford sediment and Ringold layers are within the published ranges (Graham et al. 1981). Figure 3.15 shows the calibrated SLAEMS model for the unconfined aquifer of the Hanford Site for June 1984.

To check the quality of the model calibration, difference maps of predicted minus observed hydraulic heads were prepared. Over most of the model domain, the difference was restricted to less than 1 m. Particular attention was given to the area near the Grout Disposal Facility.

Another indication of the quality of calibration was comparison of travel times. The travel time from the Grout Disposal Facility to the Columbia River was determined to be approximately 32 years. This figure compares favorably with the times projected by other investigators (USGS 1987).

Figure 3.15. Calibrated Unconfined Aquifer Model Based on SLAEMS for June 1984

3.4.4.3 Post-Hanford Unconfined Aquifer Model Applications

To simulate post-Hanford conditions, the artificial recharge from Hanford operations was removed. It was also assumed that the 200 East and 200 West Areas would be allowed to revegetate and the infiltration and subsequent recharge rates would decrease. All other boundary conditions (e.g., prescribed heads along the rivers) remained the same. Figure 3.16 shows the potential values for post-Hanford groundwater for the unconfined aquifer.

3.4.5 Transport in the Unconfined Aquifer

The SLAEMS model was applied to conduct a travel time and pathline analysis used to provide "well intercept factors" for domestic and community well scenarios. The model was also used to predict travel times to the Columbia River for discharge of contaminated groundwater to the river.

Figure 3.16. Post-Hanford Conditions Predicted With SLAEMS

The model was run using two scenarios: current conditions with the present amount of precipitation and recharge, and a wetter case scenario that assumes an additional 5 cm of recharge applied over the entire Hanford Site. Figures 3.17 and 3.18 show the water table elevations and pathlines to the river for both cases. The shortest time necessary to travel from the Grout Disposal Facility to the Columbia River was determined for both scenarios and is shown in Table 3.20. The increased recharge causes the pathway to the river to change and results in a longer travel time.

Additional applications were done with a well placed 100 m from the boundary of the grout site. A pumping rate of $45 \text{ m}^3/\text{d}$ ($1.2 \times 10^4 \text{ gal/d}$) was used to simulate the water use for a 2-hectare (5-acre) farm. The exact placement of the well depended on the recharge rates and subsequent flow patterns. The well was placed in the center of the plume created by the grout site to intercept as much of the plume as possible. The width of the intercept and the width of the plume were determined. The time necessary to travel from the boundary of the grout site to the well was determined for both scenarios. Table 3.20 shows the results of the simulation runs.

Figure 3.17. Water-Table Elevations and Pathlines Predicted With SLAEMS for Current Recharge Conditions

Figure 3.18. Water-Table Elevations and Pathlines Predicted With SLAEMS for Additional 5 cm/yr Recharge Conditions

Table 3.20. Summary of SLAEMS Model Simulations

Case	Aquifer Thickness (m)	Plume Intercept (m)	Plume Width (m)	Hydraulic Gradient (m/m)	Travel Time,		Ground-water Flux (m ³ /d)	Well Intercept Factor
					100-m Well (days)	River (years)		
Calibration	27.46					31.7		
R = 0.1 cm/yr Q _w = 0	21.3	--	256	4.18 x 10 ⁻⁴	478	37.5	24.6(a)	0.010
R = 0.1 cm/yr Q _w = 45 m ³ /d	21.1	(72 x 2) = 144 ^(c)	255	4.76 x 10 ⁻⁴	333		45 ^(b)	0.00308
R = 5 cm/yr Q _w = 0	25.21	--	416	3.1 x 10 ⁻⁴	645	36.4	29.7 ^(a)	0.415
R = 5 cm/yr Q _w = 45 m ³ /d	25.07	(80 x 2) = 160 ^(c)	416	3.9 x 10 ⁻⁴	378		45 ^(b)	0.105

(a) Upper 4.6 m of aquifer.

(b) Well pumping rate.

Notes: R = recharge rate; Q_w = well discharge, K_{sat} = saturated hydraulic conductivity = 50 m/d.

(c) Factor of 2 is due to the influence of anisotropic hydraulic conductivities on plume intercept determined using PORFLOW model.

The quantity of groundwater receiving contamination from the Grout Disposal Facility was determined in the following manner:

- Low pumping rate:

$$\text{Well-intercept factor} = \frac{(\text{infiltration through the facility, } 0.245\text{-m}^3/\text{d})}{(\text{width of aquifer intercept}) \times (\text{depth of screen}) \times (\text{Darcy velocity})} \quad (3.9)$$

where infiltration through the Grout Disposal Facility is a function of the 0.1-cm/yr recharge rate over an area of approximately 90,000 m². For the 5-cm/yr recharge rate cases, the 0.245-m³/d factor in Eq. (3.9) is replaced by 12.3-m³/d. This definition of well-intercept factor for the low pumping rate cases assumes that the contamination infiltrating into the aquifer from the Grout Disposal Facility is distributed uniformly and results in a uniform or average concentration in a rectangular cross-section of aquifer.

- Pumping rate for the 45 m³/d rate:

$$\text{Well-intercept factor} = \frac{(\text{fraction of grout plume intercepted} \times 0.245 \text{ m}^3/\text{d})}{(\text{groundwater well pumping rate of } 45 \text{ m}^3/\text{d})} \quad (3.10)$$

Equation (3.10) applies to the 0.1-cm/yr infiltration rate cases. For the 5-cm/yr recharge rate cases, the 0.245-m³/d factor in Equation (3.10) is replaced by 12.3-m³/d.

A combination of homogeneous isotropic and homogenous anisotropic analyses were used to define the areal and vertical influence of a partially penetrating well in the vicinity of the Grout Disposal Facility at Hanford. By design, the pumping well used for the groundwater scenarios partially penetrates the aquifer. Aquifer properties are often heterogeneous and anisotropic (i.e., they vary with spatial location and direction). Field data do not allow incorporation of small-scale heterogeneities into the regional model. However, an anisotropic ratio of horizontal-to-vertical hydraulic conductivity between 16 to 1 and 13 to 1 has been reported for the unconfined aquifer in the 200 Areas (Graham et al. 1981).

While the SLAEMS code used for the regional unconfined aquifer model is able to address the anisotropic nature of the aquifer by introducing distinct stratigraphic layers, it is unable to address the effects of the partially penetrating well. Consequently, the PORFLOW^(a) code was used to evaluate the local effect of a partially penetrating well pumped at 45 m³/d in an aquifer with an assumed horizontal-to-vertical hydraulic conductivity ratio of 15 to 1. A 5-km by 5-km (3.1-mi by 3.1-mi) water table aquifer approximately 20-m (65.6-ft) thick was used for the evaluations. The unconfined aquifer model based on SLAEMS was used for benchmark comparison for a fully penetrating well. The results of the evaluation are presented in Table 3.21 in terms of plume intercept width 100-m (328-ft) upgradient from the well (i.e., at the disposal site). The plume intercept width is the maximum width of influence of the well where all of a contaminant plume would be intercepted.

Table 3.21. Plume Intercept Width (m) at 100 m Upgradient of a Pumping Well

Aquifer Property	Partially Penetrating Well	Fully Penetrating Well
Isotropic	83.2 m (PORFLOW)	61.9 m (PORFLOW) 61.25 m (SLAEMS)
Anisotropic	113 m (PORFLOW)	61.3 m (PORFLOW) 60.65 m (SLAEMS)

(a) PORFLOW is copyrighted by Analytic and Computational Research, Inc., subject to Limited Government License.

The PORFLOW results confirm the performance of fully penetrating and partially penetrating wells in both isotropic and anisotropic aquifers. The trend in the results is as anticipated; the most narrow intercepts are for the fully penetrating wells and the widest intercept is for a partially penetrating well in an anisotropic aquifer. The results reveal a greater width by approximately a factor of 2 for the more realistic case of a partially penetrating well in an anisotropic aquifer, as compared with the prediction of the fully penetrating well in an isotropic aquifer. Thus, the results for the SLAEMS model simulation as listed in Table 3.20 were adjusted by a factor of 2 (see footnote (c) in Table 3.20).

In addition to evaluating impacts from the hypothetical well, the predictions of flow paths and travel times for radionuclides to reach and discharge to the Columbia River were evaluated. The quantity of radionuclides entering the river annually through groundwater flow was assumed to be diluted by a volume of water corresponding to the annual average river flow rate at Priest Rapids Dam (Woodruff, Hanf, and Lundgren 1992). This assumption requires the further assumption of complete mixing by the river. Although this is not a realistic assumption for the Hanford Reach of the Columbia River above Richland and possibly as far downstream as McNary Dam, contaminants that enter the river from groundwater flow at Hanford are likely mixed downstream of McNary (Walters, Dirkes and Napier 1992).

3.5 Modeling Approach and Codes

This section describes the modeling approach and codes used to quantify radionuclide release from the grout waste form, transport in the unsaturated sediments, interception by a groundwater well or transport to the Columbia River, and exposure and dose to humans. The interrelationships between codes used in this performance assessment are illustrated in Figure 3.19 and described in terms of data required and results produced by the individual codes. Each code is then briefly described and the rationale for its selection presented. Four codes were employed in this performance assessment: PORFLOW, SLAEMS, CCSUMRY-PF, and GENII. PORFLOW and SLAEMS were applied to the unsaturated sediments and the unconfined aquifer. CCSUMRY-PF was used to simply combine inventory and decay data with results from the unsaturated sediment and unconfined aquifer analyses. GENII was used to apply the exposure scenarios and assess the health impacts to future residents of the site and region.

S9211085.58

Figure 3.19. Integration of Computational Methods and Computer Codes Used in the Grout Performance Assessment

3.5.1 Modeling Approach

The Grout Disposal Facility was assessed using a decoupled suite of codes (see Figure 3.19). The decoupled components of the analysis involved a separate analysis of the surface barrier, unsaturated sediments (including the engineered disposal system), unconfined aquifer, and exposure and dose to humans.

Deterministic models were employed, thus providing a single response to a set of model parameters. Models of the unsaturated and aquifer components of the system were based on porous media concepts. For both the unsaturated sediment and unconfined aquifer analyses, perturbations to parameter values defined cases used to explore the influence of design elements and model parameters. A more rigorous Monte Carlo approach was taken to determine the sensitivity of results to parameters employed in the exposure and dose assessment.

Because of the large number of radionuclides in the inventory, a method was needed to reduce the simulations to a manageable number. The method used was to identify groups of radionuclides and associate them with conservative transport properties for each group. This was done for both the grouted waste and the natural sediments. In general, radionuclides in grout were classified into four groups ranging from mobile to successively more sorbed. In the natural environment, their transport mobility was also classified into four groups. Overall, the inventory was divided into seven groups which conservatively represent the mobility in both grout and sediments.

3.5.1.1 Surface Barrier

Analyses of the surface barrier were performed under the research program currently developing the permanent isolation barrier for the Hanford Site (see Appendix F). Their research considers relationships between climate, vegetation, surface soils, small and large mammals, and wind erosion and soil deposition. Results of research have demonstrated that silt loam surface soils can recycle precipitation to the atmosphere through evaporation if vegetation is not present, or through evapotranspiration in the presence of vegetation. It has been demonstrated that up to double the amount of precipitation can be recycled, thus producing the conditions that prevent infiltration through the surface barrier system. The current design goal of the permanent isolation barrier program is 0.05 cm/yr.

Analysis of the surface barrier response to variations in climate, vegetation, and soils requires detailed, often hourly or daily, input data. Therefore, for this performance assessment it was decided to reference the research results of the permanent isolation barrier program and its design goal, rather than to perform independent and duplicate analyses. Incorporating the surface barrier and its requisite detailed data into the overall unsaturated zone analysis would be prohibitively expensive. Simulations of the unsaturated sediment pathway have employed 0.1-cm/yr, i.e., double the design goal, as the recharge rate through the surface barrier. Additional discussion of the recharge rate can be found in Section 2.7 and Appendix F.

3.5.1.2 Engineered Disposal System and Unsaturated Sediments—PORFLOW Code

The unsaturated profile between the base of the vaults and the water table of the unconfined aquifer is approximately 60-m (200-ft) thick. Flow in the unsaturated sediment pathway is an important component of the pathway analysis. The PORFLOW code was used to simulate water flow and contaminant transport in the engineered disposal system and the unsaturated profile.

The geometry of the profile analyzed is defined by the size and location of engineered structures and barriers, and the thickness of geologic features such as distinct sediment layers. Models of the unsaturated sediments require specification of hydraulic model parameters that define the movement of water, and transport model parameters that define the migration of contaminant. The flow of water was modeled with Darcy's equation as modified for the unsaturated zone by Richards (1931). The hydraulic models and their parameters describe the water retention and relative hydraulic conductivity relationships of the unsaturated media based on the models of van Genuchten and Mualem (Mualem 1976, van Genuchten 1980). Parameters required by the hydraulic model for each material (or porous media) are the saturated hydraulic conductivity, saturated moisture content, residual moisture content, and two fitting parameters for the van Genuchten-Mualem soil water retention model, α and n . Contaminant transport is by advection, diffusion, and sorption. Water velocities required for the advection model are provided by the water flow analysis. Sorption of contamination in grout and on sediments has been modeled using the linear sorption isotherm. Parameters required by transport models for each material type are the effective diffusion coefficient, distribution coefficient, particle or grain density, and total porosity (if different than saturated moisture content). Cases involving the staged degradation of the engineered system must provide the required hydraulic and transport data for each stage of degradation.

Each contaminant transport analysis is initialized as a unit source of contamination in the grouted waste region of the model. In the majority of cases, the flow and transport analysis within the unsaturated zone provided an estimate of water and relative contaminant flux to the water table. In the case of the zero-recharge, or upward diffusion analysis, concentrations of contamination were estimated in the surface soil profile. In either case, the results from the PORFLOW code were passed to the CCSUMRY-PF code.

3.5.1.3 Unconfined Aquifer—SLAEMS Code

Underlying the unsaturated sediments is the unconfined aquifer. It forms the next segment in the subsurface pathway to the accessible environment and human exposure. The time scale of transport in the unsaturated zone is on the order of hundreds to thousands of years, while that in the aquifer is on the order of tens of years. Because of the relatively short travel time for contaminants in the unconfined aquifer, a pathline and travel-time approach was taken to model contaminant migration in the aquifer. The SLAEMS code has been used to simulate the unconfined aquifer and estimate the pathlines followed by contamination, and to estimate contaminant travel times to groundwater wells and the Columbia River.

Data requirements of the unconfined aquifer model include the identification of boundaries, internal geologic structure, internal sources and sinks of water, hydraulic properties of the porous media, and water table elevations. The aquifer is bounded by relatively impermeable basalt formations, the Columbia and Yakima rivers, and lateral recharge regions defined as Dry Creek and Cold Creek Valleys. Details of these boundaries and how they were addressed can be found in Section 3.4.4. The internal structure and its associated hydraulic properties were defined by specifying the position and thickness of two distinct hydrologic units, the Hanford and Ringold formations. The hydraulic properties required by the model were saturated hydraulic conductivity and porosity. Conductivity values were allowed to vary spatially by defining zones of constant property value. These zones captured both areal and vertical variability in conductivity. Calibration of the model used an approximate steady-state system existing in the mid 1980s. Thus, internal sources and water table data from this period were used to establish this model of the unconfined aquifer.

After calibration, the model was modified to represent future conditions by stripping off all industrial discharges associated with operation of the Site. Cases involving water supply wells located 100-m downgradient of the Grout Disposal Facility, and different recharge rates, were studied. Particle-tracking methods were used to establish travel times to locations of interest [100-m well (328 ft) and the Columbia River]. Pathlines were also used to trace the boundary of contamination, and, hence, determine the fraction of a contaminant plume intercepted by a water supply well and the width of aquifer contaminated by releases from the Grout Disposal Facility. These analyses ultimately defined a well intercept factor for specific recharge rates and pumping rates. Similarly, pathlines were used to characterize the transport of contamination to the river in terms of travel time. Results of the SLAEMS analysis of the unconfined aquifer, i.e., travel time and well intercept factors, were provided to the CCSUMRY-PF code.

3.5.1.4 CCSUMRY-PF

Efficiencies were obtained by uncoupling the analyses of the unsaturated sediment profile and the unconfined aquifer; however, ultimately the analyses must be combined to produce estimates of water quality in the water supply well, contaminant flux to the Columbia River, or soil contamination in surface sediments. CCSUMRY-PF combines input from PORFLOW and SLAEMS with the total inventory and decay half-life data. It then produces a table of water quality, groundwater flux, or soil contamination levels as a function of time for the scenario being simulated. These data are provided to the exposure and dose calculation.

3.5.1.5 Exposure and Dose to Humans—GENII

This final segment of the analysis applies exposure scenarios and assesses dose impacts to future generations. The exposure scenarios described in Section 3.2 and Appendix M have already influenced the analysis by defining the subsurface pathways and the points in the environment accessible to future inhabitants. Parameter selections in the exposure model define the human exposure from the food eaten and the environment lived in, and result in estimates of dose from exposure to radioactivity.

The scenarios examined assess exposures to near-term (<500 years) intruders, and to long-term future inhabitants of the site. The intruder scenarios were a drilling scenario resulting in acute exposure to an individual, and a post-drilling habitation scenario resulting in chronic exposure to a family. Long-term exposures and dose were evaluated for a variety of scenarios based on the use of water from the aquifer (i.e., irrigated farm, irrigated garden, drinking water, and community well), the use of water from the Columbia River, the habitation of land contaminated by the upward diffusion of radioactive waste, and the habitation of land contaminated by a cataclysmic glacial flood (erosion-deposition) event. Calculated doses were compared to performance objectives for the disposal action. The performance objectives were described in Chapter 1.

3.5.2 Unsaturated Flow and Transport Code: PORFLOW

Version 2.394gr of the PORFLOW computer code (Sagar and Runchal 1990, Runchal and Sagar 1992) was used to simulate flow and contaminant transport from the Grout Disposal Facility through the unsaturated zone to the unconfined aquifer and upward to the land surface. Specifically, the code was used to quantify the movement of water through the backfill, RCRA cover, gravel layer, vault structure, surrounding soils, and underlying formations. Transport processes of contaminant advection, diffusion, and sorption were included in the simulations.

3.5.2.1 Description of PORFLOW

PORFLOW is a software package for solving problems involving multiphase fluid flow, heat transfer, and mass transport in variably saturated, porous, and fractured porous media. Some of the attributes of PORFLOW are:

- capability to model either single or multiphase flow
- applicability to one-, two-, or three-dimensional geometries in Cartesian or cylindrical coordinate systems
- availability of alternate solution techniques (including point successive over-relaxation, Cholesky decomposition, Gauss elimination, and reduced system conjugate gradient)
- availability of multiple porosity representations
- availability of discrete features (such as boreholes or fractures) that are represented by line or plate elements.

The PORFLOW computer code is written in FORTRAN-77 and runs on personal computers and workstations. For calculations in this performance assessment, however, a CRAY XMP was used with simulations typically lasting 10 to 25 hours or more. Appendix G provides an expanded description of the theoretical framework and the input/output of PORFLOW.

3.5.2.2 Selection and Background of PORFLOW

The PORFLOW computer code was selected for modeling unsaturated flow and transport in grout after considering the code's theoretical framework, implementation of the theory, documentation, quality control, acceptability by the technical community, and computational speed. Additional detail is provided in Appendix G. The theoretical framework of PORFLOW is based on appropriate fundamentals of physics, hydrology, and geochemistry and is applicable to problems of unsaturated flow. Specific modifications were made to the code, allowing simulation of degraded engineered barriers, to make a version (2.394gr) applicable to this performance assessment. Sufficient documentation (Runchal and Sagar 1992) and quality assurance backup (Piepho et al. 1994) exist for the code. The PORFLOW "family" of codes (version 2.394gr and its predecessors) has been used extensively across the DOE complex, and is generally accepted by the technical community. The computational speed of PORFLOW is such that simulations could be made on the CRAY with acceptable turnaround time.

The original version of PORFLOW (Kline et al. 1983 and Runchal et al. 1985) was limited to modeling saturated conditions in two-dimensional porous media. The code was modified to simulate variably saturated (unsaturated) flow in three dimensions and was termed PORFLO-3, version 1.0 (Runchal and Sagar 1989; Sagar and Runchal 1990). Version 2.0 added the capability to treat multiphase problems. Version 2.394gr was used in this performance assessment. This version includes changes made specifically for grout performance assessment calculations. A newer version (i.e., Version 2.1) to treat multiphase problems was developed for DOE and is the basis of the version used in this performance assessment.

3.5.2.3 Verification and Benchmarking of PORFLOW

Verification and benchmarking of PORFLOW is described in Appendix H and in Piepho et al. (1994). Software quality assurance (QA) for PORFLOW was followed according to the WHC QA procedures (WHC 1992a) and software practices (WHC 1993a).

Verifying the suitability of the computational grid employed in an analysis is an important aspect of any simulation. The unsaturated-zone cross section simulated for this performance assessment is depicted in Figure 3.2. A computational grid has been superimposed on the engineered design. The computational grid used in the numerical simulations, defined by a rectangular array of blocks in the horizontal and vertical directions, was based on the following guidelines.

1. There must be at least three contiguous blocks within each material that appears in a given horizontal row of blocks. Similarly, there must be at least three contiguous blocks within each material in any vertical column of blocks.
2. The maximum block aspect ratio should not exceed 10--that is, for any block in the grid the length-to-width ratio (or width-to-length ratio) must not exceed 10.

3. The grid spacings should not change by more than a factor of 2 from its neighbors.
4. Grid spacing should remain constant near vertical and horizontal material boundaries. Block boundaries are defined in PORFLOW as midway between specified block centers.

These guidelines were imposed to reduce the amount of numerical dispersion in the simulations. Figure 3.20 illustrates the grid used for the numerical simulations. The grid violates guideline 3 at one place where $\Delta z_i = 2.12 \Delta z_{i-1}$ and at another place where $\Delta z_i = 2.12 \Delta z_{i+1}$. The minimum and maximum Δx are 10 cm and 97.14 cm, respectively. Similarly, the minimum and maximum Δz are 10 cm and 100 cm, respectively. There are 77 grid blocks in the x-direction and 162 grid blocks in the z-direction for a total of 12,474 blocks. This number does not include so-called "border" or "pseudoblocks" employed by PORFLOW in the two-dimensional plane being analyzed.

A coarse and a fine grid were used in the PORFLOW verification/benchmark study (Piepho et al. 1994). No significant differences were revealed in a comparison of results from those two grids. The coarse grid used in that study was similar to one used in the performance assessment. Because the grid used in the performance assessment was intermediate in size compared to those used in the PORFLOW verification study, more sensitivity analyses concerning grid size were not considered necessary. All sensitivity cases are described in another supporting document (Piepho 1994).

An automatic convergence control feature in the PORFLOW code was used in all simulations. As a result, the convergence criteria selected for the pressure variable (e.g., varied from 1×10^{-4} to 1×10^{-6} for the cases simulated) was always met at each time step before moving to the next. With this feature, if the convergence criteria are not met after a set number of iterations, the time step is cut and the simulation for the time step restarted. This approach increases computer simulation times, but also ensures convergence criteria are met.

3.5.2.4 Validation of PORFLOW

Validation of flow and transport models for predicting long-term impacts over thousands of years has been difficult because data are generally not available to carry out such an exercise (Bredehoeft and Konikow 1993). Presently, none of the revisions of PORFLOW have been validated for unsaturated flow by comparison to Hanford laboratory or field data. The predecessor to PORFLOW Version 1.0, PORFLO-3, Version 5.7, was validated for coupled head and saturated fluid flow with laboratory data (Runchal et al. 1985). PORFLO-3 was calibrated with field data and used to simulate flow and transport of strontium-90 from a trench in the 100-N Area to the Columbia River. Other validation exercises have been performed with an older version of PORFLO-3 for simulation of flow and transport at an experimental trench in Las Cruces, New Mexico (Wittmeyer and Sagar 1992a, b).

Figure 3.20. Numerical Grid Used in PORFLOW for the Grout Performance Assessment

Water Table

ent with an Insert Showing the Relative Position of Engineered Structures and Sediment Layers

3.5.3 Saturated Flow and Pathline Transport Code: SLAEMS

SLAEMS (Strack 1989) was used for the analysis of saturated flow and pathline transport in the unconfined aquifer. SLAEMS (Single Layer Analytical Element Method-Stratified) is based on the analytic element method and models the flow in detail for the region of interest (beneath the grout site and toward the river) and with diminishing emphasis at greater distances away from the region of importance. SLAEMS is an extension of the SLAEM code that allows for multiple layers of different hydraulic conductivity within the regional aquifer. Transport is limited to an advection-only approximation and uses pathlines and particle tracking to estimate travel times.

The analytic element method involves superposition of closed-form analytic functions representing individual features of an aquifer. Developing the approach involves identifying available theoretical, closed-form solutions, and adapting them to the range of hydrologic features that occur in practical, heterogeneous groundwater applications. These analytic expressions for hydrologic elements are compiled in a modular form into a computer code that provides the individual hydrologic elements and a capability to superimpose them and model complex aquifers.

3.5.3.1 Description of the SLAEMS Code

SLAEMS incorporates numerous analytic elements to model areal infiltration (recharge), rivers, wells, ponds, and isolated features such as canals and impermeable objects. Inhomogeneities are used to model zones in the regional aquifer that exhibit changes in the hydrogeology, e.g., base elevation, thickness or number of layers, or hydraulic conductivity.

Results can be viewed either graphically or in tabular form. The analytic element method generates a continuous field of two-dimensional potential (head values) and stream function (streamlines), allowing the user to redefine the window of inspection to investigate any portion of the regional aquifer. Graphics capabilities allow plotting of the potential or stream functions. The graphics package allows particle tracing based on this approximation. Particle tracing and streamline plots provide a means of analyzing contaminant movement. The areal influence of a source can be traced within the groundwater system, and travel times from source to exposure can be estimated. SLAEMS incorporates a module for checking the numerical solution.

3.5.3.2 Selection and Background of SLAEMS

The analytic element code SLAEMS was selected to simulate the unconfined aquifer because of its flexibility and efficiency. The code provides a spatially continuous solution, eliminating the need for a discrete grid. The SLAEMS code can be used to focus on detail in a small region of interest, such as the Grout Disposal Facility, with diminishing interest and less detail at distances away from the facility.

The analytic element modeling method is a new application of some of the oldest groundwater modeling techniques. The method includes techniques for modeling areal and vertical heterogeneities. It

is based on closed-form analytical expressions for the particular subsurface hydrologic features to be modeled in the groundwater system. The theory behind the code, numerous analytical elements, and the first version of the modeling capability can be found in Strack (1989).

3.5.3.3 Verification and Validation of SLAEMS

In this performance assessment, verification of SLAEMS involved comparing alternate analytical solutions (e.g., Thiem equation, method of images) with those of the model. Differences in the head values predicted by the model and alternate analytical solutions were less than the 1% error accountable to numerical inaccuracies. In the strict sense, classical verification of the SLAEMS code is complicated by the fact that SLAEMS is based on the analytic element method. Classical verification involves comparing two different solutions to the same problem; one obtained from the numerical code and the other from an analytical solution. However, SLAEMS is based on, and includes, those closed-form analytical expressions.

Analytical elements may be linked or combined in a variety of ways. By nesting, overlapping, or linking different elements (e.g., an impermeable wall nested within an inhomogeneity zone) it is possible to model complicated aquifer systems. An advanced form of verification done on SLAEMS involved determining the total steady-state groundwater flux for a predefined region in a complex problem. The difference between the flux entering and leaving the specified window was less than a 1% error for the cases examined.

The SLAEMS code has an established facility for verification during application to a particular problem. Control points can be used to specify boundary conditions for a model based on SLAEMS. These points, which are specified by the user, can be checked against values computed by the code. The differences between specified and computed values should be less than a 1% error.

Applications of the SLAEMS code to sites other than Hanford are documented in Strack (1989). Several of the applications described by Strack involved comparison of predicted to observed conditions in natural aquifer systems. These documented applications provide assurance that the SLAEMS code is properly coded and valid. For the Hanford Site application, the model was calibrated against measured hydraulic heads in the unconfined aquifer from June 1984.

3.5.4 CCSUMRY-PF

A utility code, Contaminant Concentration SUMmary-PF (CCSUMRY-PF), was used to combine information from the PORFLOW unsaturated-zone simulations with inventory information and groundwater modeling results from the SLAEMS code for preparing well and river concentration data for dose calculations. The modifier "-PF" denotes the version associated with PORFLOW. The code is used to

translate unsaturated-zone modeling results for a single vault in two dimensions to 33 vaults in three dimensions. Output consists of radionuclide concentrations in water pumped from a well or in water entering the river over time.

CCSUMRY-PF was used to assemble the results produced by unsaturated zone flow and transport computations, groundwater flow and travel time simulations, and individual contaminant inventory data into contaminant arrival distributions at locations downgradient from the Grout Disposal Facility. Radioactive decay occurring from the time of site closure (time zero) is also accounted for in CCSUMRY-PF.

Travel times within the saturated zone were small relative to those found in the vadose zone (Gee et al. 1992). It was assumed that the travel times from the entry point at the water table to the downgradient locations are constant with time. The downgradient locations were 1) a pumped well where the contaminant is mixed in the well bore before environmental accumulation and exposure, and 2) the Columbia River. In subsequent dose calculations, the groundwater contaminant flux arriving at the Columbia River is mixed with the $3,400 \text{ m}^3/\text{s}$ flow rate of the river.

As previously described, the unsaturated-zone region simulated was a two-dimensional vertical cross section of the actual problem; a three-dimensional rectangular parallelepiped containing a single grout vault. This vertical cross section was assumed to have a unit thickness, to pass through the grout vault, and to have "average" properties of the three-dimensional problem. The vertical cross section, sometimes called a "computational slice" where flow and transport calculations were made, was shown previously in Figure 3.2. The water table is located at the bottom of the unit slice. The vadose zone flow and transport analysis provides the dimensionless rate at which contamination enters the aquifer. The fractional release rate to the aquifer is $d(Q/Q_0)/dt$ where Q_0 is the initial mass of contaminant within the slice and $d(Q/Q_0)$ is the fraction of the initial inventory released to the aquifer during the time period dt . The rate of fractional release of inventory to the aquifer as a function of time serves as the input to CCSUMRY-PF. The fractional release for the computational slice was scaled directly to the fractional release for the field of vaults. This approach implies that the scale-up within a vault is based on the length of the vault and neglects any effect caused by the ends of the vaults. Scale-up based on length is reasonable because of the greater importance of advection compared to diffusion in release of contaminants from the vault. Also, scaling on a basis such as total vault surface area would release more than the initial amount of mass.

At any specific moment in time, the product of $d(Q/Q_0)/dt$ and the initial total site inventory for a given waste species is the amount of that inventory item released to the groundwater by the entire disposal system. This product was converted to a concentration by dividing by the volume of the disposal site recharge to the aquifer, Q_{gw} . This concentration was further modified by a well intercept factor that accounts for mixing of contaminated recharge in the aquifer. If the downgradient location of interest is not a well, the well intercept factor is not applied in CCSUMRY-PF. Radioactive species were decayed; the decay time is the travel time in the unsaturated zone plus the travel time in the unconfined aquifer.

These travel times included any retardation from adsorption. This final quantity of water pumped from the well or discharged to the Columbia River specifies concentrations of individual species at a specific moment in time.

CCSUMRY-PF was checked by hand calculations to ensure the calculations were being performed properly by the code. The code is under configuration management.

3.5.5 Dose Calculations: GENII Code

Doses resulting from human exposure to radionuclides disposed in grout were calculated with the GENII environmental dosimetry software system for complex exposure pathways such as the irrigated garden, or with published dose factors (U.S. DOE 1988b) for the simple dose calculations based on consumption of drinking water. For the complex exposure pathways in the intruder, groundwater, and surface water scenarios, the GENII code was used to generate "scenario dose factors" based on unit radionuclide concentrations in the grouted waste, soil, or downgradient water supplies. The scenario dose factors were then multiplied by the applicable radionuclide concentration in the environmental medium of interest to obtain the final dose to an individual or population for that scenario. This approach was adopted to allow the dose calculations to proceed simultaneously with groundwater modeling and development of the final radionuclide inventories for grouted waste.

3.5.5.1 Selection and Background of the GENII Code

GENII was selected to calculate exposure and dose for this performance assessment because it was developed specifically for Hanford Site applications and incorporates dosimetric and metabolic models recommended by the ICRP.

The GENII environmental dosimetry software system (Napier et al. 1988) was developed at PNL to consolidate and update earlier pathway and dose codes used at the Hanford Site, and to implement dosimetry models recommended by the ICRP (ICRP 1977, 1979-1988, 1986). The ICRP recommendations have also been adopted for use by DOE (U.S. DOE 1990b). The code may be used to calculate dose for all significant exposure pathways based on chronic or acute radionuclide releases to air or water, or from initial radionuclide concentrations in various environmental media. In this performance assessment, the option to calculate doses from water or soil concentrations predicted with the PORFLOW, SLAEMS, and CCSUMRY-PF codes was used. Inhalation and ingestion dose conversion factors are used to determine the dose from internally deposited radionuclides. GENII accounts for radioactive decay of the parent radionuclide and buildup of daughter products in the environment. Appendix I presents a more complete description of the GENII computer code as implemented for this analysis.

3.5.5.2 Environmental Accumulation Parameters and Dose Conversion Factors

Radiation dose from radionuclide concentrations in environmental media is calculated with concentration ratios, transfer factors, and dose conversion factors. Concentration ratios are used to estimate

radionuclide concentrations in vegetation from root uptake in soils. Transfer factors are used to calculate radionuclide concentrations in animal products resulting from ingestion of radionuclides by animals through feed and drinking water. GENII contains a library of default parameters for use when other data are not available. Most of the default values were generated to be appropriate for the Hanford Site. For analysis of the Grout Disposal Facility, a more comprehensive database from a review of current literature by Kennedy and Streng (1992) was used.

Dose conversion factors are radionuclide-specific parameters that represent the dose resulting from a unit intake, or exposure to a unit-concentration source, of a radionuclide. Five different types of radionuclide dose conversion factors were used in the grout performance assessment. Inhalation and ingestion dose conversion factors are internal. External dose conversion factors are used to quantify the dose from exposure to radionuclides in surface soil, buried waste, or by immersion in contaminated water. The internal dose conversion factors used here are based on models recommended in the ICRP Publications 26, 30, and 48 (ICRP 1977, 1979-1988, and 1986), and internal and external dose conversion factors are published in two DOE publications (U.S. DOE 1988a, 1988b).

The GENII package of codes was developed under a Quality Assurance (QA) plan based on the American National Standards Institute (ANSI) standard NQA-1 (ASME 1986) as implemented in the PNL Quality Assurance Manual PNL-MA-70. (*Procedures for Quality Assurance Program*, PNL-MA-70, is a controlled document used internally at the Pacific Northwest Laboratory (PNL); information regarding the manual may be obtained from PNL in Richland, Washington.) Development of the code was documented and tested at each stage by extensive hand calculations. The code was verified and tested. Separate external peer reviews of the internal dosimetry portions of the code and of the entire code package were conducted during the development stages, and the recommendations of the review committees were incorporated into the final product. Validation is being performed by participation in the International Atomic Energy Agency Validation of Model Predictions (VAMP) program.

3.6 Case Descriptions

The purpose of this performance assessment is to estimate the potential exposure and incremental dose from the release and migration of low-level radioactive waste disposed in a grout waste form. Both near-term exposures to intruders and long-term exposures to individuals in the vicinity of the facility are of interest.

The pathways and scenarios described in Section 3.2 revealed that the subsurface pathway, including both the unsaturated zone and the unconfined aquifer, is the primary transport pathway conducting contamination to the accessible environment and humans. Dominant processes and associated models for the release and migration of contamination were described, and model parameters presented, in Sections 3.3 and 3.4 for simulating the performance of the existing engineered and natural systems. Degradation processes expected to alter the engineered system, and estimates of the associated timing and magnitude of degradation, were also described in Section 3.3. The general modeling approach and the

codes employed in simulations were presented in Section 3.5. This section will summarize the data applied in two key or central simulations, and describe specific details for each of the cases analyzed. The results are presented in the next chapter.

This performance assessment was conducted through a series of computer simulations to model the long-term performance of the Grout Disposal Facility. The simulations were used to follow the movement of contaminants from the grout, through the vault and asphalt barrier, and through the soils and sediments to the groundwater beneath the disposal site. Specific simulations (or cases) were run to compare to performance objectives, evaluate design features, and evaluate model sensitivities.

A set of four compliance cases was run to evaluate the long-term performance of the disposal system in terms of the performance objectives outlined in Chapter 1. These compliance cases included the gradual degradation of the grout, vault, and asphalt barrier from cracking and biodegradation of the asphalt. The cases included a central compliance case and cases with delayed cracking of the vault and asphalt, reduced structure resolution, and a composite model of cracking.

The five design cases help determine the role of individual components in the engineered system and identify those that most significantly influence the long-term exposure and dose estimates. This knowledge serves to define those system components whose physical, hydraulic, and transport properties to be further studied. The design cases evaluated the roles of the grout waste form, vault, asphalt barrier, gravel layer above the asphalt barrier, and the RCRA cover.

Numerous sensitivity cases were modeled to understand the effect of inherent material properties on the overall system performance. These properties include contaminant retardation coefficients, unsaturated hydraulic properties, saturated hydraulic properties, degradation rates, and degradation locations. The sensitivity cases also considered the impacts of a higher water infiltration rate. Ranges of these properties are modeled to quantify the impact on public exposure. The relative change in dose resulting from property changes is a measure of the sensitivity.

The remainder of this section presents the general set of model parameters applied in the central sensitivity and central compliance cases, and the details specific to each case necessary to describe the results presented in Chapter 4. Hydraulic and transport model data are compiled in tables for the central sensitivity and central compliance cases. All other compliance, design, and sensitivity cases are then presented in terms of how they differ from their respective central case. In this last subsection, where details of individual cases are described, the compliance cases are presented first. They are followed by related cases that examine specific issues such as radon release or upward diffusion, and these are followed by the central sensitivity case, design cases, and sensitivity cases. Results from simulation of the compliance cases are compared to the performance objectives and appear first in Chapter 4. The design and sensitivity cases support the compliance cases by providing insight into the system responses.

3.6.1 Hydraulic and Transport Properties of the Central Sensitivity Case

Hydraulic and transport properties for intact components of the engineered system were presented in Section 3.3. Degradation mechanisms and degraded states for these same components were also described. This section summarizes the data employed in a case that is central to the analysis, the central sensitivity case. In this case, hydraulic and transport properties were fixed for all time with the exception of those for the asphalt barrier. Those properties changed after 90,000 years when the asphalt barrier was assigned the hydraulic and diffusion properties of backfill soil. This case is central to other cases used to study the influence of engineered components of the design, and the sensitivity of results to hydraulic and transport model parameters. Additional details about this case and others related to it are presented later in this section.

Cases related to this central case are based on the philosophy that the performance of engineered and natural system components can be studied on a comparative basis using perturbations from a central case that does not include several stages of degradation. The perturbations addressed here involved the absence or presence of components (e.g., barriers or elements of the natural system) and ranges of hydraulic and transport model parameters. The central case for purposes of these comparisons was the central sensitivity case. Its conceptual model and suite of hydraulic and transport properties are summarized below.

3.6.1.1 Conceptual Model of the Central Sensitivity Case

The vertical cross section analyzed in this case was bounded left and right by symmetry boundaries, and above and below by the base of the permanent isolation barrier and the water table (see Figure 3.2). The components of the engineered system modeled were the RCRA cover, a partial gravel layer, backfill soil, asphalt barrier, concrete vault, and grout. Details of the HDPE flow net, thermal insulation board, catch basin, and sump were not simulated; these components were modeled as part of the concrete vault. Three significant aspects of the case which define its overall release were 1) gravel was placed only in the region immediately above the concrete vault/asphalt barrier; 2) cracks were defined in horizontal and vertical planes in the upper corners, and horizontal cracks in the lower corners of both the asphalt barrier and concrete vault; and 3) asphalt in the asphalt barrier was completely biodegraded in 90,000 years.

Gravel Layer. While the design calls for a continuous layer of gravel to be placed above the pair of vaults sharing a RCRA cover, all analyses have associated gravel properties only with the region immediately above the vault. Regions above and to the left and right of the gravel layer were assigned the properties of the backfill soil. Such a configuration of soil property assignments will allow more infiltration to drain to the left of the vault than is expected to occur if the gravel is continuous to the left symmetry boundary.

Horizontal and Vertical Cracks. Regions defined as cracks were placed in the corners of the concrete and asphalt components of the structure based on experience in the design and failure modes of structures, i.e., professional judgement. Initially, cracks would be on the scale of millimeters; however,

their width could increase with time. To simplify the central sensitivity case, a single computational cell was assigned the properties of the crack. (Sensitivity cases described in Section 3.6.5.3 studied the possible influence of crack widths smaller than a single cell using equivalent property relationships for flow and diffusion parallel to layers of different materials.)

The hydraulic and transport properties of the unsaturated and cracked concrete and the asphalt barrier materials are unknown. To ensure that hydraulic and transport properties assigned to these zones of the analysis did not control the analysis, an equivalent porous media model was adopted and cracks were assigned the properties of the backfill soil. All horizontal cracks interface with backfill soil as the surrounding soil type, and, thus, adopting soil properties eliminates an interface between properties at the exterior of the structure. In addition, because of the pore structure and wettability of soils, water will readily flow through the soil. This treatment was assumed to be conservative regarding the hydraulics of discrete fractures in either concrete or asphalt barrier materials. Cracks may be discrete (e.g., present an air gap with occasional points of contact between surfaces) and unsaturated water flow is impeded by air gaps. Furthermore, asphalt is not wet by water, and, therefore, it is unlikely that it will transmit liquid water under unsaturated conditions. To maximize the cracks' potential influence, they were configured to be a direct path from the grout and through both the concrete vault and asphalt barrier to the surrounding backfill soil and gravel.

Biodegradation. Biodegradation of asphalt was considered as a method of completely removing the asphalt from the asphalt barrier. Measured rates of biodegradation for the asphalt are approximately 1×10^{-4} cm/yr (Luey and Li 1993). Using a simple two-sided biodegradation model (e.g., interior and exterior surfaces) implies complete biodegradation in 500,000 years. Thus, assuming complete biodegradation after only 90,000 years is conservative. It is unlikely that biodegradation will completely remove the asphalt; however, the properties of backfill soil were assigned to the asphalt barrier region after 90,000 years.

As biodegradation occurs at surfaces of the asphalt barrier, the portion of the barrier containing asphalt decreases and the portion of simple aggregate increases. This assumes biodegradation completely removes the asphalt and leaves behind only the aggregate. Furthermore, it is assumed the pore structure of the aggregate remains unchanged, i.e., the total porosity remains equal to 0.202. The aggregate is modeled, as elsewhere in this conceptualization, as backfill soil because of the similarities in their engineering specifications (e.g., grain size distributions). Diffusion through the asphalt barrier moves orthogonally to layers of intact asphalt barrier and the biodegraded asphalt barrier. An equivalent effective diffusion coefficient can be defined for either an individual computational cell or the entire barrier thickness, as represented by several computational cells. The equivalent parameter, as a function of the diffusion coefficients and thicknesses for each layer, was calculated according to classical theory (Crank 1975, pg. 267). This particular parameter was updated continuously (at each time step) during the simulation. Because diffusion is orthogonal to the layers and the effective diffusion coefficient in the intact asphalt barrier is quite low (1×10^{-10} cm²/s), biodegradation of the barrier must be nearly complete before the equivalent effective diffusion coefficient significantly increases. Therefore, equivalent parameters

were established on the basis of the entire barrier thickness, thus reducing the number of equivalence calculations and the complexity of property updating (e.g., all asphalt barrier computational cells were updated simultaneously).

3.6.1.2 Summary of Hydraulic and Transport Properties

The properties of intact engineered system and existing unsaturated zone profile are presented in Table 3.22. Components of the engineered system identified in the table include the asphalt barrier after

Table 3.22. Summary of Hydraulic and Transport Properties for the Central Sensitivity Case

Material	K_{sat} (cm/s)	Porosity ^(a)	θ_s	θ_r	α (cm ⁻¹)	n	D_{ab} (cm ² /s)	a	b
Asphalt Barrier									
t < 90,000 yr	1×10^{-20}	0.162	0.162	0.0	1.0×10^{-5}	2	1×10^{-10}	1	0
t ≥ 90,000 yr	3×10^{-2}	0.202	0.371	0.045	0.0683	2.08	2.5×10^{-5}	0.005	10
Asphalt Cracks	3×10^{-2}	0.3710	0.371	0.045	0.0683	2.08	2.5×10^{-5}	0.005	10
Reinforced Concrete	3.75×10^{-10}	0.2258	0.2258	0.0	7.61×10^{-6}	1.393	5×10^{-8}	1	0
Concrete Cracks	3×10^{-2}	0.3710	0.371	0.045	0.0683	2.08	2.5×10^{-5}	0.005	10
Grout	1.47×10^{-8}	0.5781	0.5781	0.0	1.08×10^{-5}	1.65	1×10^{-6}	1	0
RCRA Cover	1×10^{-7}	0.448	0.448	0.0	5.39×10^{-4}	1.324	2.5×10^{-5}	0.005	10
Gravel Layer	1.85	0.518	0.518	0.014	3.5366	2.661	2.5×10^{-10}	1	0
Backfill Soil	3×10^{-2}	0.371	0.371	0.045	0.0683	2.08	2.5×10^{-5}	0.005	10
Hanford Formation									
- Sandy Sequence	1.55×10^{-3}	0.4203	0.4203	0.0234	0.1943	1.868	2.5×10^{-5}	0.005	10
- Gravel Sequence	2.73×10^{-4}	0.3584	0.3584	0.0213	0.0290	1.613	2.5×10^{-5}	0.005	10
Ringold Formation	2.42×10^{-6}	0.4982	0.4982	0.0283	0.0176	1.338	2.5×10^{-5}	0.005	10

- (a) The PORFLOW code requires the porosity, or saturated moisture content, to be input along with residual saturation, which is defined as θ_r/θ_s . For the asphalt barrier after 90,000 years, the porosity value entered was 0.202, indicating a biodegraded barrier. The residual saturation and other unsaturated soil characteristics are of a backfill soil; e.g., $\theta_r/\theta_s = 0.1213$. Thus, backfill soil hydraulic characteristics are applied to determine saturation levels in the asphalt barrier aggregate, which has a total porosity of 0.202.

90,000 years, asphalt cracks, and concrete cracks. Each of these subregions of the model domain were assigned the properties of backfill soil. The properties assigned to the Hanford and Ringold formations are also provided in the table.

Sorption was associated only with the grout and natural sediments, including backfill soil. However, sorption was not included in any crack regions or in the biodegraded asphalt. The sorption properties assigned to grout, backfill soil, and the Hanford and Ringold formations are summarized in Table 3.23. The code used to simulate water flow and contaminant transport in the unsaturated zone calculated the retardation factor (R) based on distribution coefficient (R_d), grain or particle density, and total porosity (or its equivalent, saturated volumetric moisture content). Values for each of these parameters are provided. Because R_d data do not exist for the spectrum of soils underlying Hanford, single conservative values of R_d were adopted to represent individual contaminants in all the soils and sediments.

Table 3.23. Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments^(a)

Group	Species	Grout R_d (ml/g)	Grout $R^{(b)}$ (-)	Soil R_d (ml/g)
1A	^3H , ^{103}Ru , $^{106}\text{RuRh}$, ^{125}Sb , ^{129}I	0	1	0
2A	^{99}Tc	2	4.82	0
2B	^{94}Nb , ^{95}Nb	2	4.82	0.67
3A	Selected chemicals only	125	240	0
3C	^{60}Co , ^{63}Ni , ^{79}Se , ^{90}Sr , ^{113}Sn , ^{126}Sn , ^{134}Cs , ^{135}Cs , ^{137}Cs , ^{226}Ra , ^{237}Np	125	240	3
4A	^{14}C , ^{234}U , ^{235}U , ^{238}U	2625	5020	0
4D	^{95}Zr , $^{144}\text{CePr}$, ^{152}Eu , ^{154}Eu , ^{155}Eu , ^{230}Th , ^{238}Pu , $^{239/240}\text{Pu}$, ^{241}Pu , ^{242}Pu , ^{241}Am , ^{243}Cm , ^{244}Cm	2625	5020	21

(a) No sorption in asphalt barrier, concrete vault, cracks in either asphalt or concrete, RCRA cover, or gravel.

(b) $R = 1 + (\rho_b R_d / \theta)$; data required to make this calculation are as follows:

Grout: Particle density = 2.62 g/ml, $\theta = 0.5781$, Bulk density (ρ_b) = Particle density $\times (1 - \theta)$

Backfill Soil	2.72	0.371
Hanford - Sandy	2.72	0.4203
Hanford - Gravel	2.72	0.3584
Ringold	2.72	0.4982

3.6.2 Hydraulic and Transport Properties of the Central Compliance Case

This section presents additional notes on the conceptualization and data employed in the central compliance case. Where in the previously described central sensitivity case the hydraulic and transport properties were fixed for all time (with the exception of those for the asphalt barrier), in the central compliance case the properties go through step changes. Each step change represents a discrete change to a more degraded state. The one exception to this approach is the treatment of water vapor diffusion, which increases linearly over the defined intervals. Additional details on this and related compliance cases follow this presentation of the general data for the central compliance case.

The central compliance case provides a central point of reference for several compliance cases. However, no single compliance case should be viewed as more or less probable than another. Special aspects of the conceptual model and the hydraulic and transport properties for the central compliance case are summarized below.

3.6.2.1 Background

The compliance case simulations included stepped or staged degradation. In these cases, at specific moments in time, the hydraulic and transport properties (or both) were altered to reflect a more degraded physical or chemical state of the engineered system. To transition the system from intact (as built) performance to fully degraded performance, several steps were taken.

To examine the potential effect of degradation, the level of degradation must be related to changes in model parameters. One approach to this problem was to forecast a level of degradation (i.e., specify the size and spacing of cracks), propose alternate models of flow and transport for degraded structures (e.g., discrete fracture, equivalent porous media, composite porous media, etc.), and evaluate the performance of the alternate models (e.g., required time step and spatial resolution to control numerical dispersion and obtain simulation accuracy). Ultimately a preferred model would be selected, and its hydraulic or transport model parameters would be selected to accurately reflect the levels of degradation.

A second approach involved fixing the end points of the performance continuum as intact (as built) and fully degraded. This was done in terms of the key hydraulic or transport property of interest. For example, the saturated hydraulic conductivity of the asphalt barrier has an intact value of 1×10^{-11} cm/s and a fully degraded value corresponding to the backfill soil, i.e., 3×10^{-2} cm/s. Parameter values between these two states were related to the assumed levels of degradation (size and spacing of cracks). Values were derived from classical equivalent formula for the porous media property of flow and diffusion parallel or orthogonal to layers (Harr 1962, pg. 27; Crank 1975, pg. 267 and 273), or they were assigned based on professional judgement. While classical methods exist for defining equivalent saturated hydraulic conductivity and effective diffusion coefficients, no methods exist to define equivalent model parameters for unsaturated hydraulic characteristics. Despite this shortcoming, the second approach was used to develop properties associated with the degradation steps for the compliance cases.

A change in the physical system should produce related changes in all hydraulic and transport properties. For example, changes in pore structure should cause related changes in conductivity, diffusion, porosity, and unsaturated hydraulic characteristics. However, concepts and modeling approaches for addressing the degradation of materials have not been developed for the unsaturated zone profile. The approach taken in this study (i.e., to simply stop the simulation, insert new hydraulic and transport properties, and restart the simulation) revealed that care must be taken to conserve mass. With the exception of the concrete medium, which showed only minor porosity alteration when cracked, the solution to the mass conservation problem was to hold the porosity constant throughout the analyses. Attempts to vary the total porosity of the asphalt barrier with the formation of cracks or biodegradation of asphalt led to significant mass balance errors.

Another observation related to changing hydraulic properties and conserving mass was the apparent release of water from a material when the material's unsaturated hydraulic characteristics were altered. Clearly, if the ability of a medium to retain water is altered by changing its air entry potential, saturated moisture content, residual moisture content, saturated hydraulic conductivity, etc., then drainage can occur as the problem domain seeks a new equilibrium. The sudden release of contaminated water from altered components of the engineered structure, or the sudden drainage of contaminated pore water from grout, can result in unrealistic surges of water and contaminant through the unsaturated sediments and into the accessible environment. To avoid such events, the unsaturated hydraulic characteristics of the backfill soil were used to calculate the relative saturation for the intact and degraded asphalt barrier, the degraded asphalt corner crack regions, and the degraded reinforced concrete. Note, the total porosity or saturated moisture content of the media were set to the values associated with each particular media. The relative saturation, at a moment in time and point in space, was applied to the total porosity of the medium to determine its associated unsaturated moisture content. The unsaturated hydraulic characteristics of grout were not altered during the simulation. While this treatment is known to be flawed from the viewpoint of basic soil physics, the separate treatment of these properties has been necessary to produce simulations.

Those components of the engineered disposal system composed of natural material (i.e., the RCRA cover, gravel layer, and backfill soil) and the undisturbed sediment profile (i.e., Hanford formation sandy and gravel sequences, and Ringold formation) have not been degraded over time. Among these materials, only the long-term performance of the gravel layer was a concern. The performance of the gravel layer as a capillary break is known to be dependent on the amount of fine soils that can infiltrate the gravel and alter its hydraulic characteristics. Tests have shown the movement of fine soils into an open gravel caused by simulated earthquakes to be a maximum of 5.1 cm (2 in.) along vertical interfaces and 12.7 cm (5 in.) along horizontal interfaces (Kramer and Holtz 1989). The gravel layer, which has not been constructed and therefore can be altered to ensure performance, will be of sufficient thickness and slope (10%) to function as a capillary break.

3.6.2.2 Conceptual Model of the Time Intervals and Associated Degradation

At most, four degradation steps have been defined and only three for the reinforced concrete vault. The first step represents a virtually intact state; the last represents maximum degradation. Simulations have been conducted by assigning the defined properties (i.e., model parameter values) at the beginning of the associated time interval. However, these properties should not be interpreted as the actual property values at the beginning of the time interval; if this were true, then the model would not account for degradation during that time period. The property values can be interpreted as averages during the time interval, or as the property values at the end of the time interval. If the latter interpretation is made, the model of degradation would be conservative, because the greatest degradation during the time interval would have been applied throughout the interval. To the extent the initial property values assigned to the first time interval are conservative, the average value interpretation applies to the compliance cases. Using the intact (as built) property values in the absence of a well-defined model of the timing and magnitude of degradation, and the relationship between degraded states and hydraulic and transport parameters, makes it inappropriate to assert the model is absolutely conservative or bounding.

A determining factor in the definition of the compliance cases and the timing of overall degradation was the time required to completely biodegrade the asphalt barrier. Complete biodegradation was modeled to require a short 40,000 years. The maximum published value of biodegradation was 1 cm/1,000 yr. If the 1-m- (3-ft-) thick barrier were to degrade on both interior and exterior surfaces, a 50,000-year period would be required for complete biodegradation. A conservative rate of biodegradation measured for the AR-6000 asphalt used in the construction of the vaults was 1.2×10^{-4} cm/yr, or 1.2 cm per 10,000 years. A value of 1 cm/10,000 years implies two-sided biodegradation would require 500,000 years. Thus, the assumed 40,000-year interval for complete biodegradation is conservative.

Based on the professional judgement of structural engineers, the upper corner of the asphalt was the most likely place for cracks to appear following degradation of the thermal insulation board and slumping of the barrier material. Discrete 5-mm horizontal and vertical cracks were placed in the upper corners of the asphalt barrier and aligned with the corner of the concrete vault. However, unlike the central sensitivity case, the concrete structure was not cracked along the same plane and, thus, a continuous crack was not created between the grout and the surrounding sediments. The presence of discrete cracks in the concrete vault at construction joints will be described in Section 3.6.3.1.

All other cracks in the asphalt barrier and concrete vault were assumed to be evenly distributed on the surfaces of the respective structure. Equivalent saturated hydraulic conductivity and effective diffusion coefficient values were applied uniformly to the surfaces. The size and spacing of these cracks, and their assignment to the backfill soil properties, define the information necessary to calculate equivalent conductivity and diffusion coefficient values.

Asphalt Barrier. The conceptual model for degradation of the asphalt barrier calls for biodegradation to act continuously, and for through-wall cracks to appear after 10,000 years. These cracks will exhibit a maximum size and minimum spacing of 1 mm on a 1-m grid in the time interval between

10,000 and 100,000 years. The time periods and assumed cracks for the asphalt barrier in the central compliance case are listed below. As noted above, the biodegradation rate assumed is clearly conservative (Table 3.24).

Asphalt Corner Cracks. The conceptual model identified 5-mm horizontal and vertical cracks in the upper corners of the asphalt barrier during the 100- to 1,000-year time interval. The time periods and assumed cracks for the asphalt corner crack regions are listed below. The crack widths are increased over time, allowing biodegradation of the crack surfaces (Table 3.25).

Reinforced Concrete. The conceptual model called for the following levels of degradation in the concrete structure:

- During the 0- to 100-year time interval, the only degradation was initial cracking of roof plank joints
- During the 100- to 1,000-year time interval, three types of degradation occurred: 1) roof plank joint cracks increased in width, 2) construction joint cracks appeared, and 3) surface cracks developed in response to rebar corrosion

Table 3.24. Crack Size/Spacing as a Function of Time for the Asphalt Barrier

<u>Time, yr</u>	<u>Crack Size and Spacing</u>
0 to 5,000	None
5,000 to 20,000	1 mm at 1 m
20,000 to 40,000	1 cm at 1 m
> 40,000	Complete biodegradation

Table 3.25. Size of Asphalt Corner Crack as a Function of Time

<u>Time, yr</u>	<u>Crack Size and Spacing</u>
0 to 100	None
100 to 20,000	5 mm
20,000 to 40,000	2 cm
> 40,000	Complete biodegradation (20 cm)

- Beyond 1,000 years, degradation continued because of the roof plank joint cracks, construction joint cracks, and surface cracking associated with increased steel corrosion. General through-wall cracks appeared in response to the weakened structure and increased seismic loads.

The time periods and assumed cracks for the reinforced concrete vault are listed in Table 3.26. Through-wall cracks appear in the model at discrete locations, e.g., construction joints, from the initialization of the simulation. The placement of through-wall cracks in the roof, walls, and floor, and nuances of property assignments for these cracks, are described in Section 3.6.3.1. General through-wall cracks appeared in the concrete structure after 5,150 years.

Grout. Degradation of the grout monolith is related to the degradation of the reinforced concrete vault. As the concrete vault degrades, as indicated by the appearance of through-wall cracks, seismic loads originally borne by the reinforced concrete structure are transferred to the grout monolith. Such loads would cause the grout monolith to fracture. For the central compliance case, this degradation was modeled at earlier times when cracks appearing in grout would be filled by precipitated solids, i.e., calcium carbonate or calcium silicate hydrates, thus re-establishing the high integrity of the waste form. At later times, the capacity to produce reaction products is expected to diminish. The approach taken to quantify the degradation of grout was to define the initial and end-state values of changing properties and select intermediate values from that range. The time intervals of the degraded states for grout were identical to those for the asphalt barrier.

3.6.2.3 Saturated Hydraulic Conductivity and Porosity

Saturated hydraulic conductivities for the different degradation states relied on the intact and fully degraded state values. When crack size and spacing was defined for a degradation interval, the equivalence formula for flow parallel to stratification was employed to define an equivalent porous media property. As noted above, the porosity assigned to materials was held constant, with the exception of that for the reinforced-concrete material.

Table 3.26. Crack Size/Spacing as a Function of Time for Reinforced Concrete

Time, yr	Crack Size and Spacing
0 to 5,150	No generalized cracking, only discrete roof and construction joint cracks at time = 0.
5,150 to 20,000	1 mm at 1 m
> 20,000	2 mm at 1 m

Asphalt Barrier. The intact conductivity value of 1×10^{-11} cm/s was based on nitrogen gas permeability measurements and represents a conservative estimate of liquid water conductivity because the viscosity of the water and the wetting properties of the asphalt barrier have been neglected. The fully degraded value was based on two assumptions: biodegradation removes all asphalt, and the conductivity of the aggregate in the asphalt barrier is analogous to that of the backfill soil, i.e., 3×10^{-2} cm/s. If all asphalt was not removed from the aggregate by biodegradation, the total porosity of the aggregate would be lower and a lower conductivity should result. Thus, use of the backfill soil value is believed to be biased toward a conservative estimate. Values of conductivity for the two intermediate time intervals were calculated using the equivalence relationship for flow parallel to stratification.

In this and other applications of the equivalence formula, the proportion of surface area devoted to cracks was defined by crack width per unit length of surface in the cross section, e.g., 1 mm of crack per 1 m (3.3 ft) of roof, wall, or floor. On a fractional basis, this implies a 1-m length of asphalt barrier surface is divided into a 0.001-m crack and 0.999 m of intact material. The true fraction would be defined on a surface area basis, i.e., 1-mm cracks on a 1-m (3.3-ft) grid would equate to two 1-mm cracks on a 1-m^2 (10.7-ft^2) surface. The corresponding fractions would be a 0.002-m^2 crack area and 0.998 m^2 of intact material. However, the former definition was employed in this analysis. For example, the saturated conductivity during the 5,000- to 20,000-year time interval was defined by the product of saturated conductivity of crack and fraction of crack space, added to the product of the bulk material conductivity and its fraction of space, i.e.,

$$K_{\text{sat}} = (3 \times 10^{-2} \text{ cm/s}) \times (0.001) + (1 \times 10^{-11} \text{ cm/s}) \times (0.999) = 3 \times 10^{-5} \text{ cm/s} \quad (3.11)$$

The saturated hydraulic conductivity for the other time interval was similarly calculated. The saturated hydraulic conductivity and porosity values for the asphalt barrier are listed in Table 3.27.

Table 3.27. Saturated Hydraulic Conductivity and Porosity of the Asphalt Barrier

Time, yr	K_{sat} (cm/s)	Porosity	Crack Size and Spacing
0 to 5,000	1×10^{-11}	0.04	None
5,000 to 20,000	3×10^{-5}	0.04	1 mm at 1 m
20,000 to 40,000	3×10^{-4}	0.04	1 cm at 1 m
> 40,000	3×10^{-2}	0.04	Complete biodegradation

The porosity for the asphalt barrier was assigned the value 0.04 and held constant throughout the simulation to ensure mass conservation. This decision was based on the source of the conductivity measurement. The nitrogen gas permeability was determined for the air void volume (i.e., the available porosity of 0.04), and water flow can occur only through this same porosity. Of course, as biodegradation removes the asphalt, the available porosity should increase to 0.202; however, based on the measured biodegradation rate, this amount of pore space would not actually be available within the entire barrier until well after 40,000 years. Sensitivity analyses were conducted comparing the use of a constant 0.04 versus a constant 0.202 porosity. Of the cases simulated, the case employing porosity of 0.04 produced slightly higher releases.

Asphalt Corner Cracks. The intact and end state values for saturated hydraulic conductivity of the asphalt barrier were applied to the corner crack regions. Similarly, the constant porosity of 0.04 was adopted. Values of saturated hydraulic conductivity were calculated using the equivalence relationship for flow parallel to stratification. The cracks were embedded in a 20-cm- (7.9-in.-) wide computational cell. The saturated hydraulic conductivity and porosity values for degraded asphalt corner crack regions are listed in Table 3.28.

Reinforced Concrete. The saturated hydraulic conductivity of intact concrete was taken as the laboratory-determined value, i.e., 3.75×10^{-10} cm/s (see Appendix J). The value for fully degraded concrete was based on the assumption of a maximum crack width of 2 mm and a minimum crack spacing of 1 m (3.3 ft) after 20,000 years. The saturated hydraulic conductivity of the crack was assigned the value for backfill soil, and the equivalence relationship for flow parallel to stratification was applied. The value of saturated hydraulic conductivity for the intermediate degradation step was similarly calculated based on a crack size and spacing of 1 mm and 1 m (3.3 ft).

Porosity of the intact reinforced concrete was also the laboratory-determined value, i.e., 0.2258. Unlike other components of the engineered disposal system, the porosity of the concrete was adjusted to reflect an increase in porosity resulting from the creation of an open crack of the defined aperture. This

Table 3.28. Saturated Hydraulic Conductivity and Porosity of the Asphalt Corner Cracks

Time, yr	K_{sat} (cm/s)	Porosity	Crack Size and Spacing
0 to 100	1×10^{-11}	0.04	None
100 to 20,000	7.5×10^{-4}	0.04	5 mm at 20 cm
20,000 to 40,000	3×10^{-3}	0.04	2 cm at 20 cm
> 40,000	3×10^{-2}	0.04	Complete biodegradation

calculation uses the same method for determining the spatial fraction devoted to a cracked region and the intact material as that employed in the equivalent conductivity calculation, i.e.,

$$\text{Porosity (at 5,150 yr)} = (1.0) \times (0.001) + (0.2258) \times (0.999) = 0.2266 \quad (3.12)$$

The end-state value of porosity was similarly defined based on the crack size and spacing. The saturated hydraulic conductivity and porosity values for degraded reinforced concrete are listed in Table 3.29.

Grout. A different approach was taken to define properties associated with the degraded states of grout. A relatively low range in saturated hydraulic conductivity was adopted for grout assuming that as fractures develop in the waste form, water movement into the fractures or in the adjacent media would result in the precipitation of minerals in the fractures or on the surfaces of the fracture, thus filling the fractures and re-establishing a low-conductivity porous medium. The saturated hydraulic conductivity of intact grout was selected to be 1×10^{-10} cm/s. This was based on scoping studies that have shown 1×10^{-10} cm/s as the value for K_{sat} on grout cores. This value needs to be confirmed in future research. The fully degraded or end-state K_{sat} value for grout was based on the assumption that aged or degraded grout would be similar to the Ringold formation sediments found at Hanford. The saturated hydraulic conductivity of Ringold formation used in this analysis was 2.42×10^{-6} cm/s (see Appendix J), and the value assigned to fully degraded grout was 1.5×10^{-6} cm/s. Order-of-magnitude changes were assigned to saturated hydraulic conductivity for the earlier time intervals of degradation. Because the grout continues to cure over time, and because any fractures are assumed to be filled by precipitated minerals, the porosity of grout was held at its measured value of 0.5781. Values of saturated hydraulic conductivity and porosity for degraded grout are listed in Table 3.30.

3.6.2.4 Unsaturated Hydraulic Characteristics

As noted in Section 3.6.2.1, to eliminate surges of water and contaminants within the unsaturated zone in response to changes in hydraulic properties, the unsaturated hydraulic characteristics were held constant after the onset of degradation. Degradation took the form of cracks in either the asphalt barrier or reinforced concrete, and in the biodegraded asphalt barrier material. With one exception as described

Table 3.29. Saturated Hydraulic Conductivity and Porosity of Reinforced Concrete

Time, yr	K_{sat} (cm/s)	Porosity	Crack Size and Spacing
0 to 5,150	3.75×10^{-10}	0.2258	None
5,150 to 20,000	3×10^{-5}	0.2266	1 mm at 1 m
> 20,000	6×10^{-5}	0.2274	2 mm at 1 m

Table 3.30. Saturated Hydraulic Conductivity and Porosity of Grout

Time, yr	K_{sat} (cm/s)	Porosity
0 to 5,000	1×10^{-10}	0.5781
5,000 to 20,000	1.5×10^{-8}	0.5781
20,000 to 40,000	1.5×10^{-7}	0.5781
> 40,000	1.5×10^{-6}	0.5781

below, the unsaturated hydraulic characteristics of backfill soil were assigned to these degraded materials. This was done because backfill soil will transmit water more readily than other media in these analyses, and therefore using the characteristics of backfill soils ensured that the hydraulics of the degraded material would not limit release.

The unsaturated characteristics listed below were used to predict the degree of saturation in the media. To obtain water content, the predicted saturation was multiplied by the porosity, which was set independently.

Asphalt Barrier. Because of the similarity assumed between the aggregate in the asphalt barrier and the backfill soil, and the absence of measured unsaturated hydraulic characteristics, the characteristics of the backfill soil were assigned to the asphalt barrier for all time. These characteristics were specified in terms of four van Genuchten-Mualem model parameters: saturated moisture content, θ_s ; residual moisture content, θ_r ; a fitted parameter, α (which physically approximates the inverse of the air entry potential); and another fitted parameter, n . These characteristics are listed in Table 3.31 for the asphalt barrier.

Asphalt Corner Cracks. The unsaturated hydraulic characteristics of intact reinforced concrete were assigned to the initial 100-year time interval. This property assignment created a continuous concrete medium from the interior surface of the concrete structure (in contact with grout) to the surrounding

Table 3.31. Unsaturated Hydraulic Characteristics of the Asphalt Barrier

Time (1,000 yr)	Porosity	Crack Size and Spacing	Unsaturated Characteristics $\theta_s, \theta_r, \alpha \text{ (cm}^{-1}\text{)}, n$
0 to 5,000	0.04	None	0.371, 0.045, 0.0683, 2.08
5,000 to 20,000	0.04	1 mm at 1 m	0.371, 0.045, 0.0683, 2.08
20,000 to 40,000	0.04	1 cm at 1 m	0.371, 0.045, 0.0683, 2.08
> 40,000	0.04	Complete biodegradation	0.371, 0.045, 0.0683, 2.08

environment. The unsaturated hydraulic characteristics of the backfill soil were applied during all other degradation time intervals. These characteristics are listed in Table 3.32 for the asphalt corner crack regions.

Reinforced Concrete. The unsaturated hydraulic characteristics of intact reinforced concrete were assigned to the initial 5,150-year time interval. The characteristics of backfill soil were applied thereafter. These parameters are listed in Table 3.33 for the degraded reinforced concrete.

Grout. The unsaturated hydraulic characteristics of intact grout (see Appendix J) were assigned to grout for the entire simulation. This was consistent with the belief that any degradation of grout leading to cracks or fractures would be followed by periods when minerals would precipitate in the cracks, fill or plug the cracks, and re-establish the unsaturated hydraulic behavior of the original material. This was also consistent with the belief that if grout does fracture, the resulting blocks of grout would retain their unsaturated characteristics and not drain substantial amounts of pore water. The characteristics for grout are listed in Table 3.34.

Table 3.32. Unsaturated Hydraulic Characteristics of Asphalt Corner Cracks

<u>Time (1,000 yr)</u>	<u>Porosity</u>	<u>Crack Size and Spacing</u>	<u>Unsaturated Characteristics</u> $\theta_s, \theta_r, \alpha \text{ (cm}^{-1}\text{)}, n$
0 to 100	0.04	None	0.2250, 0, 7.61×10^{-6} , 1.393
100 to 20,000	0.04	5 mm at 20 cm	0.371, 0.045, 0.0683, 2.08
20,000 to 40,000	0.04	2 cm at 20 cm	0.371, 0.045, 0.0683, 2.08
> 40,000	0.04	Complete biodegradation	0.371, 0.045, 0.0683, 2.08

Table 3.33. Unsaturated Hydraulic Characteristics of Reinforced Concrete

<u>Time (1,000 yr)</u>	<u>Porosity</u>	<u>Crack Size and Spacing</u>	<u>Unsaturated Characteristics</u> $\theta_s, \theta_r, \alpha \text{ (cm}^{-1}\text{)}, n$
0 to 5,150	0.2258	None	0.2250, 0, 7.61×10^{-6} , 1.393
5,150 to 20,000	0.2266	1 mm at 1 m	0.371, 0.045, 0.0683, 2.08
> 20,000	0.2274	2 mm at 1 m	0.371, 0.045, 0.0683, 2.08

Table 3.34. Unsaturated Hydraulic Characteristics of Grout

<u>Time (1,000 yr)</u>	<u>Porosity</u>	<u>Unsaturated Characteristics</u>
		$\theta_s, \theta_r, \alpha \text{ (cm}^{-1}\text{)}, n$
0 to 5,000	0.5781	0.5781, 0, 1.08×10^{-5} , 1.65
5,000 to 20,000	0.5781	0.5781, 0, 1.08×10^{-5} , 1.65
20,000 to 40,000	0.5781	0.5781, 0, 1.08×10^{-5} , 1.65
> 40,000	0.5781	0.5781, 0, 1.08×10^{-5} , 1.65

3.6.2.5 Transport Parameters

The principal transport parameter is the effective diffusion coefficient. Concepts identical to those applied to define saturated hydraulic conductivity were applied to determine diffusion coefficient values. The other key transport process model employed in these analyses was the linear sorption isotherm model, which represents the adsorption-desorption and precipitation-dissolution of contaminants. Aside from the grout waste form, sorption was neglected in the engineered components of the disposal system. With respect to the reinforced concrete, this was a conservatism in the analysis. Sorption model parameters for grout were described in Section 3.3.3.1 and summarized in Table 3.3.

Asphalt Barrier. An effective diffusion coefficient of $1 \times 10^{-10} \text{ cm}^2/\text{s}$ was applied to the first degradation period. This was a conservative estimate for diffusion through asphalt based on literature and laboratory measurements. This effective diffusion coefficient value applies to the bulk medium, and its application to transport through only the asphalt phase without adjustment for the associated pore space was a conservatism in the analysis. In the central sensitivity case, the concentrations within the barrier were assumed to occur within the 16.2 volume percent of the asphalt barrier occupied by asphalt. However, in the central compliance case, the concentrations were modeled as occurring in a water phase within the 4 volume percent air void of the asphalt barrier. This approach was used to prevent the unrealistic drainage of moisture (which originally represented asphalt) that was observed in the central sensitivity case when the barrier was degraded. Transport through the 4% void of the barrier was modeled by setting the porosity of the barrier to 0.04 and assigning it the water retention properties of backfill soil. As transport occurs within a smaller volume fraction of the asphalt barrier, less diffusive flux is required to raise the concentration within the asphalt barrier. Thus, modeling diffusion as occurring through a smaller volume fraction of the asphalt barrier accelerates the rate at which a transient diffusion profile is established within the barrier. However, if evaluated with constant concentration boundary conditions on either side of the asphalt barrier, the two treatments provide the same diffusive flux at steady-state. Because of the accelerated development of the transient diffusion profile, the approach in the central sensitivity case is believed to be slightly conservative. However, because of the relative importance of transport by advection and the transport through cracks, the amount of conservatism introduced is believed to be small.

Diffusion coefficients for the degraded states were based on the assumptions that 1) diffusion through cracked and biodegraded asphalt barrier material can be conservatively modeled as diffusion through the liquid water phase in backfill soil, 2) an effective diffusion coefficient for an equivalent porous medium can be defined using the classical method for diffusion parallel to stratigraphic units, and 3) diffusive transport occurs through the same void space (void content = 0.04) employed in the hydraulic model. The effective diffusion coefficient in water, $2.5 \times 10^{-5} \text{ cm}^2/\text{s}$, was applied to the liquid water phase in backfill soils. This coefficient was corrected (i.e., reduced) for unsaturated conditions when applied to unsaturated soils and sediments in this analysis; however, such a correction was not made within the degraded asphalt barrier.

The effective diffusion coefficient for the fully degraded state (after 40,000 years) is generally defined by the product of the diffusion coefficient in liquid water and the volumetric water content of the medium. It was defined using the volumetric asphalt content, i.e., 16.2% by volume in these calculations. The resulting calculation follows:

$$D_e = (2.5 \times 10^{-5} \text{ cm}^2/\text{s}) \times (0.162) = 4.05 \times 10^{-6} \text{ cm}^2/\text{s} \quad (3.13)$$

This created an effective diffusion coefficient suitable for application to biodegraded asphalt barrier materials with a saturation of 80.2% (i.e., $0.162/0.202$). The effective diffusion coefficients for the other time intervals were similarly calculated. The values of effective diffusion coefficient for the degraded asphalt barrier are listed in Table 3.35.

Asphalt Corner Cracks. The end-state value of the effective diffusion coefficient and the method of calculating the equivalent effective diffusion coefficients for the asphalt corner cracks were identical to those described in the paragraphs above for the asphalt barrier. However, the initial effective diffusion coefficient was set to a value consistent with an existing 5-mm crack (i.e., $D_e = 1 \times 10^{-7} \text{ cm}^2/\text{s}$). This is justified because of the short duration of the low diffusivity performance, and because the value applied is

Table 3.35. Effective Diffusion Coefficients for the Asphalt Barrier

<u>Time (1,000 yr)</u>	<u>$D_e \text{ (cm}^2/\text{s)}$</u>	<u>Porosity</u>	<u>Crack Size and Spacing</u>
0 to 5,000	1×10^{-10}	0.04	None
5,000 to 20,000	4.15×10^{-9}	0.04	1 mm at 1 m
20,000 to 40,000	4.05×10^{-8}	0.04	1 cm at 1 m
> 40,000	4.05×10^{-6}	0.04	Complete biodegradation

conservative with respect to the intact material property, i.e., $D_e = 1 \times 10^{-10} \text{ cm}^2/\text{s}$. Values of effective diffusion coefficient are listed in Table 3.36 for the degraded asphalt corner crack regions.

Reinforced Concrete. The effective diffusion coefficient assigned to the initial time interval was that of an intact concrete. Values associated with degraded states were equivalent coefficient values based on the volume fraction of crack associated with the D_e of water, and the remaining volume fraction associated with the D_e of intact concrete. For example, the effective diffusion coefficient for the intermediate degradation step is calculated as

$$\begin{aligned} D_e &= (0.001 \times (2.5 \times 10^{-5} \text{ cm}^2/\text{s}) + (0.999) \times (5.0 \times 10^{-8} \text{ cm}^2/\text{s})) \\ &= 7.5 \times 10^{-8} \text{ cm}^2/\text{s} \end{aligned} \quad (3.14)$$

Note, the D_e value assigned to the fully degraded state was calculated during preliminary studies and used a crack density of 4 mm per 1 m (3.3 ft) of surface. The resulting value was carried into these simulations. It overestimated the effective diffusion coefficient by 50%, and was therefore conservative. The effective diffusion coefficient values for degraded concrete structures are listed in Table 3.37.

Table 3.36. Effective Diffusion Coefficients for Asphalt Corner Cracks

<u>Time (1,000 yr)</u>	<u>D_e (cm²/s)</u>	<u>Porosity</u>	<u>Crack Size and Spacing</u>
0 to 100	1×10^{-7}	0.04	None
100 to 20,000	1×10^{-7}	0.04	5 mm at 20 cm
20,000 to 40,000	4.05×10^{-7}	0.04	2 cm at 20 cm
> 40,000	4.05×10^{-6}	0.04	Complete biodegradation

Table 3.37. Effective Diffusion Coefficients for Reinforced Concrete

<u>Time (1,000 yr)</u>	<u>D_e (cm²/s)</u>	<u>Porosity</u>	<u>Crack Size and Spacing</u>
0 to 5,150	5×10^{-8}	0.2258	None
5,150 to 20,000	7.5×10^{-8}	0.2266	1 mm at 1 m
> 20,000	1.5×10^{-7}	0.2274	2 mm at 1 m

Grout. The effective diffusion coefficient for grout was $5.78 \times 10^{-7} \text{ cm}^2/\text{s}$ with the driving force modeled in the pore solution of the grout. This corresponds to a $1 \times 10^{-6} \text{ cm}^2/\text{s}$ value based on the bulk volume of grout and takes into account the degradation of grout diffusivity related to high-temperature curing. Because it already represented a highly degraded grout, the effective diffusion coefficient was held constant throughout the simulation.

3.6.2.6 Water Vapor Diffusion

As described in Section 3.3.5.2 (and Appendix P, Section P.1.1), water will diffuse toward the high salt content wastes in the vapor phase in response to the water vapor density gradient. It was shown that an intact barrier would allow 0.36 L/yr of water to diffuse to the waste and condense on vault surfaces; however, a single crack 1-cm wide running the length of the vault would produce 0.534 L/yr. Clearly, as cracks develop and as crack surfaces biodegrade, water movement to the vault surfaces through cracked and biodegraded material will be far greater than that through intact asphalt. Therefore, intact asphalt barrier surfaces were neglected in estimates of water vapor diffusion incorporated in simulations.

Because the movement of water vapor is not explicitly modeled by the PORFLOW code, the rate at which water will be drawn to the waste form was estimated in hand calculations. These rates were converted to volumetric water sources for specific computational cells immediately adjacent to discrete cracks and grout surfaces. Sources related to asphalt corner cracks were placed in the individual computational cells associated with discrete horizontal or vertical cracks. Water vapor diffusion in response to the generalized cracking of the asphalt and concrete was addressed as a uniformly distributed source over a surface rather than as point or individual cell sources associated with individual cracks. Each computational cell on such a surface was assigned the same source value (i.e., source strength was specified in $\text{m}^3/(\text{m}^3\text{-yr})$ units).

To be consistent with the derived values for saturated hydraulic conductivity and effective diffusion coefficients, the same timing and magnitude of asphalt barrier degradation was employed in water vapor diffusion calculations. A total porosity of 0.202 was employed for a completely biodegraded asphalt barrier because it is a maximum, and therefore conservative, estimate of the air pathway through biodegraded material. The rate at which water is transmitted to the vault surface is a function of porosity. Open fractures or cracks with a porosity of one yield a correspondingly higher rate than an aggregate pathway with a porosity of 0.202.

The combined effects of cracks in the barrier and biodegradation of the barrier were modeled as a single source within computational cells. Our original conceptual model was that once discrete cracks appeared, biodegradation of crack surfaces began and the cross section of the affected region or surface increased. However, the initial crack was an open pathway (porosity = 1.0) while the biodegraded asphalt barrier was represented by an aggregate pathway (porosity = 0.202). Because the open cracks make up a relatively small portion of the water vapor diffusion pathway, an aggregate pathway was assumed in the calculation of sources for the simulations.

As with the parameters described earlier in this section, the degradation assumed for a time interval is applied from the beginning of the time interval. However, the treatment of a source in the PORFLOW code zone was somewhat different than the treatment of process model parameters. Where model parameters experienced discrete steps and were discontinuous at steps, source strength was modeled as a continuous function by linearly interpolating (i.e., ramping) source strength between entered values.

Distributed Sources for Generalized Cracking and Biodegradation. Generalized cracking and biodegradation of the asphalt barrier led to the assignment of volumetric water sources to computational cells in the concrete vault immediately adjacent to the grout. A distributed water source was applied over the top of the vault and along the sides of the vault adjacent to 122 cm of uncontaminated grout (the cold cap) and the upper 155 cm of contaminated grout (upper 17% of contaminated grout). The water source was applied only to the upper region of the vault for two reasons. First, the water source has the greatest impact when added to a region where advection enters the grout. Adding water to a region where advection exists the grout dilutes the contamination leaving the grout. The water source was placed in a region in which it was known that advection primarily enters the grout. However, the region defined may not include all portions of the vault where advection enters the grout. The second reason was to avoid a mass balance problem that existed in previous simulations in which water sources were introduced into cracks containing significant concentrations of contaminants.

As noted above, the sources were applied in cells adjacent to the grout monolith; however, the rate of water movement through a degraded asphalt barrier was calculated for a pathway through only the asphalt barrier, i.e., 91.4 cm (3 ft). The resulting rates described in Section 3.3.5.2 were applied in the performance assessment as a conservative estimate of water transmission by vapor diffusion. Use of the longer pathway through both the asphalt barrier and concrete vault would have produced a lower estimated water transmission rate.

The source strength associated with generalized cracking and biodegradation was a function of the rate of water movement in the vapor phase through an aggregate, the surface area of concrete or grout exposed by cracking or biodegradation, and the total volume of the computational cell. Water movement through an open crack was estimated to be $0.1442 \text{ cm}^3/(\text{cm}^2\text{-yr})$, and water vapor diffusion through the biodegraded barrier material is proportional to the porosity (potential air void space) within the aggregate. Therefore,

Rate of water movement through a 1-cm^2 surface area

$$\begin{aligned}
 &= [0.1442 \text{ cm}^3/(\text{cm}^2\text{-yr})] \times [0.202] \\
 &= 0.0292 \text{ cm}^3/(\text{cm}^2\text{-yr}).
 \end{aligned}
 \tag{3.15}$$

The influent computational cells were those that bordered the upper surface of the grout monolith (1539.3 cm) (50.5 ft) and the upper 276.84-cm (9.1-ft) portion of the monolith walls. Total length of influent surface in the cross section analyzed was 2.09×10^3 cm. A unit (1-m, 100-cm) (3.3-ft) thickness of cross section was analyzed, so the total surface area for the influent surface was 2.09×10^5 cm². Widths of these computational cells were on the order of 11.6 cm (4.6 in.), and the volume associated with the upper surface was 1.8×10^6 cm³; that associated with each of the upper wall surfaces was 3.2×10^5 cm³. Assuming an aggregate pathway, the maximum rate at which water will be drawn to the surface by vapor diffusion is

Rate of water movement to influent surface^(a)

$$\begin{aligned} &= [0.0292 \text{ cm}^3/(\text{cm}^2\text{-yr})] \times [2.09 \times 10^5 \text{ cm}^2] = 6.10 \times 10^3 \text{ cm}^3/\text{yr} \\ &= 6.10 \text{ L/yr} = 6.10 \times 10^{-3} \text{ m}^3/\text{yr}. \end{aligned} \quad (3.16)$$

To convert this rate of water movement to a source strength for the simulation, the required source of water (i.e., 6.10×10^{-3} m³/yr) was divided by the volume of the computational cells, e.g.,

Source strength in m³/(m³-yr)

$$\begin{aligned} &= [6.10 \times 10^{-3} \text{ m}^3/\text{yr}] / [(2 \times 3.2 \times 10^5 \text{ cm}^3 + 1.8 \times 10^6 \text{ cm}^3)] \\ &= [6.10 \times 10^{-3} \text{ m}^3/\text{yr}] / 2.44 \times 10^6 \text{ cm}^3 = [6.10 \times 10^{-3} \text{ m}^3/\text{yr}] / 2.44 \text{ m}^3 \quad (3.17) \\ &= 2.50 \times 10^{-3} \text{ m}^3/(\text{m}^3\text{-yr}). \end{aligned}$$

Using this source strength for a completely biodegraded asphalt barrier, lesser amounts of cracking and biodegradation are approximated by scaling this source strength to the fraction of surface available for water vapor diffusion. The source strengths for the time periods of interest are listed in Table 3.38. The last column provides a comparison to an alternate interpretation of the generalized crack—that the initial crack presents an open pathway and that subsequent biodegradation presents an aggregate pathway. This conceptualization more closely resembles the original conceptualization and employs the more

-
- (a) By comparison, the 1-m (3.3-ft) cross section containing the engineered system was 34.9-m (115-ft) wide, and the cross section used here was 1-m (3.3-ft) thick. The recharge rate applied at the upper surface of the cross section, 0.1-cm/yr, produced 3.5×10^4 cm³/yr, or 34.9 L/yr (9.2 gal/yr) of direct infiltration.

Table 3.38. Calculated Source Strength of Water Vapor Diffusion for Generalized Cracks/ Biodegradation and Associated Surface Exposure. Not applied directly to central compliance case; see Table 3.40.

Time (1,000 yr)	Crack/Biodegradation (size and spacing)	Surface Fraction	Source Strength (aggregate pathway) [m ³ /(m ³ -yr)]	Source Strength (1-mm crack, remainder aggregate) [m ³ /(m ³ -yr)]
0 to 5,000	None	0.0	0	0
5,000 to 20,000	1 mm at 1 m	0.001	2.5×10^{-6}	1.24×10^{-5}
20,000 to 40,000	1 cm at 1 m	0.01	2.5×10^{-5}	3.49×10^{-5}
>40,000	Complete biodegradation	1.0	2.5×10^{-3}	2.51×10^{-3}

conservative open crack for a portion of the water vapor pathway. In this alternate interpretation, the initial open crack was 1-mm wide on a 1-m (3.3-ft) spacing. Both interpretations produce approximately 6.1 L/yr (1.6 gal/yr) of water within the source cells.

Computational Cell Sources for Asphalt Corner Cracks. The rates of water vapor diffusion through open and aggregate-filled space were the same as previously calculated because all calculations consider diffusion through the asphalt barrier. The rates are $0.14442 \text{ cm}^3/(\text{cm}^2\text{-yr})$ and $0.0292 \text{ cm}^3/(\text{cm}^2\text{-yr})$, respectively. Where previously these rates were applied to entire surfaces, in the case of the asphalt corner cracks they are applied to individual computational cells. There are four distinct cracks and the computational cells are on the order of 20 cm (7.9 in.) on a side (i.e., in centimeters the cell edges were 21.69×21.30 , 18.91×22.88 , 18.94×22.88 , and 21.73×21.30). Including the 100-cm (3.3-ft) depth of each cell, the total media volume was $1.8 \times 10^5 \text{ cm}^3$. The average cell edge interfacing with the concrete vault was 20.11 cm. This was judged to be sufficiently close to 20 cm (7.9 in.) to permit use of this uniform value in the calculations applied to all four cells.

The maximum rate at which water is drawn to a 20-cm by 100-cm (7.9-in. by 3.3-ft) surface through an aggregate-filled pathway is

Rate of water movement through each corner cell

$$\begin{aligned}
 &= [0.0292 \text{ cm}^3/(\text{cm}^2\text{-yr})] \times [20 \text{ cm} \times 100 \text{ cm}] \\
 &= 58.4 \text{ cm}^3/\text{yr}.
 \end{aligned}
 \tag{3.18}$$

The four corner cells have a combined water flux of $2.34 \times 10^2 \text{ cm}^3/\text{yr}$ (i.e., 0.234 L/yr or $0.234 \times 10^{-3} \text{ m}^3/\text{yr}$). This volumetric rate of water movement to source strength for the model was converted by dividing source strength by computational cell volume, i.e.,

Source strength in $\text{m}^3/(\text{m}^3\text{-yr})$

$$\begin{aligned}
 &= [0.234 \times 10^{-3} \text{ m}^3/\text{yr}] / [1.8 \times 10^5 \text{ cm}^3] \\
 &= [0.234 \times 10^{-3} \text{ m}^3/\text{yr}] / 0.18 \text{ m}^3 \\
 &= 1.30 \times 10^{-3} \text{ m}^3/(\text{m}^3\text{-yr}).
 \end{aligned}
 \tag{3.19}$$

This source strength for a completely biodegraded asphalt corner computational cell was used to scale the lesser amounts of cracking and biodegradation associated with early times. The source strengths for the time periods of interest are listed in Table 3.39. The last column provides a comparison to the alternate interpretation lent to the generalized cracks and biodegradation. In this case, the initial open crack is more substantial, 5-mm wide on a 20-cm spacing (7.9-in.), and this strongly influenced the resulting source strength estimates. The source strength associated with a 20-cm (7.9-in.) open crack was estimated as $6.44 \times 10^{-3} \text{ m}^3/(\text{m}^3\text{-yr})$ [i.e., $1.30 \times 10^{-3} \text{ m}^3/(\text{m}^3\text{-yr}) \times [0.14442/0.0292]$]. The two interpretations (i.e., aggregate only and combined crack and aggregate) would introduce 0.234 L/yr and 0.257 L/yr of water to the asphalt corner crack region of the cross section.

Source Strengths Employed in the Central Compliance Case. Tables 3.40 and 3.41 show the source strength values used in the central compliance case for influent surfaces that experienced generalized cracking, and for asphalt corner crack regions. These sources were calculated using an aggregate model and neglected the initial open crack phase. Clearly, greater source strength values were

Table 3.39. Calculated Source Strength of Water Vapor Diffusion for Asphalt Corner Cracks/Biodegradation and Associated Surface Exposure. Not applied directly to central compliance case; see Table 3.41.

Time (1,000 yr)	Crack/Biodegradation (size and spacing)	Surface Fraction	Source Strength (aggregate pathway) [$\text{m}^3/(\text{m}^3\text{-yr})$]	Source Strength (1-mm crack, remainder aggregate) [$\text{m}^3/(\text{m}^3\text{-yr})$]
0 to 100	None	0.0	0	0
100 to 20,000	5 mm at 20 cm	0.025	3.25×10^{-5}	1.61×10^{-4}
20,000 to 40,000	2 cm at 20 cm	0.1	1.30×10^{-4}	2.59×10^{-4}
>40,000	Complete biodegradation	1.0	1.30×10^{-3}	1.43×10^{-3}

Table 3.40. Source Strength of Water Vapor Diffusion for Generalized Cracks and Biodegradation as a Function of Time Interval and Associated Surface Exposure

Time (1,000 yr)	Crack/Biodegradation (size and spacing)	Surface Fraction	Source Strength [m ³ /(m ³ -yr)]
0 to 5,000	None	0.0	0
5,000 to 20,000	1 mm at 1 m	0.001	2.9×10^{-6}
20,000 to 40,000	1 cm at 1 m	0.01	2.9×10^{-5}
>40,000	Complete biodegradation	1.0	2.9×10^{-3}

Table 3.41. Source Strength of Water Vapor Diffusion for Asphalt Corner Cracks and Biodegradation as a Function of Time Interval and Associated Surface Exposure

Time (1,000 yr)	Crack/Biodegradation (size and spacing)	Surface Fraction	Source Strength [m ³ /(m ³ -yr)]
0 to 100	None	0.0	0
100 to 20,000	5 mm at 20 cm	0.025	7.29×10^{-5}
20,000 to 40,000	2 cm at 20 cm	0.1	2.9×10^{-4}
>40,000	Complete biodegradation	1.0	2.9×10^{-3}

applied than are presented above for the aggregate model. It is also clear that source strengths during the second and third period underestimate the alternative interpretation that includes the influence of discrete cracks.

3.6.2.7 Summary of Hydraulic and Transport Properties

A summary of parameter inputs to the numerical model used for the central compliance case is provided in Table 3.42 in the following section (Section 3.6.3.1). The water sources included for water vapor diffusion are not included in this table; they are listed in Tables 3.40 and 3.41, with the locations at which these sources were applied illustrated in Figure 3.21. (See Section 3.6.3.1 for Figure 3.21.)

3.6.3 Compliance Cases

The groundwater pathway results for this performance assessment are based on a series of simulations termed the compliance cases. The compliance cases model the system degradation over time using a series of step changes in the material properties of the engineered system. Because the progression of long-term degradation of the grout and engineered system is not well known, the compliance cases have been adopted as a set for comparing results to performance objectives rather than attempting to reach consensus on a single "best-estimate" case. The compliance cases are centered around the central compliance case. Other compliance cases are similar, although changes have been made in the modeling approach.

3.6.3.1 Central Compliance Case

The details of the timing and the numerical values for step changes in the properties of the central compliance case (Case 1.0) were provided in Section 3.6.2. Figure 3.21 shows a conceptual sketch of the central compliance case problem showing the features within the model of the engineered system. Table 3.42 summarizes the input for the central compliance case. The following paragraphs summarize details of the treatment of each system component.

Asphalt Barrier. In the conceptual model of the performance of the asphalt barrier, transport through the barrier occurs by diffusion in the asphalt phase and by vapor diffusion of moisture through the intact barrier material. To facilitate the degradation of the asphalt barrier within the code, the water retention properties were initially set to values derived from the backfill soil (see Section 3.6.2) and the porosity of the asphalt barrier was set to 0.04 (corresponding to the initial maximum void content). For modeling purposes, the calculation of diffusion through the barrier occurs through the 0.04 void space of the diffusion barrier. The water retention properties of the asphalt barrier were held constant throughout the simulation, while the saturated hydraulic conductivity was degraded in stages over 40,000 years from $1 \times 10^{-11} \text{ cm}^2/\text{s}$ to $0.03 \text{ cm}^2/\text{s}$.

At 100 years, 0.5-cm horizontal and vertical cracks were placed through the diffusion barrier in line with the top corners of the concrete vault. These cracks were given water retention properties of the backfill soil and a hydraulic conductivity of $7.5 \times 10^{-4} \text{ cm/s}$ in the direction of the crack. The diffusion coefficient in these cracks was $1 \times 10^{-7} \text{ cm}^2/\text{s}$; this was implemented from the start of the problem rather than at 100 years. The remainder of the barrier remains largely intact with a hydraulic conductivity of $1 \times 10^{-11} \text{ cm/s}$ until 5,000 years, at which time the entire barrier was given a saturated conductivity of $3 \times 10^{-5} \text{ cm/s}$ based on the presence of a 1-mm crack every meter. The hydraulic conductivity and diffusivity of the asphalt barrier was increased again at 20,000 and 40,000 years to account for growth in crack sizes resulting from biodegradation.

Concrete Vault. At the beginning of the simulation, the concrete was modeled as having cracks in the concrete roof and at the construction joints in the floor and walls. At five locations along the vertical walls, rows of nodes were modeled as containing cracks and were given a saturated hydraulic conductivity of 0.03 cm/s in the direction of the crack and the diffusional parameters of the backfill soil. Similarly, in the bottom of the vault, a single crack was given a hydraulic conductivity of 0.03 cm/s in both directions. The floor crack runs between the grout and the catch basin gravel.

The cracks in the roof of the concrete vault were treated slightly differently than cracks in the rest of the vault. The water retention characteristics of the concrete roof were initially set to those of the backfill soil to prevent drainage of the concrete pore water onto the vault when the concrete is degraded later in the problem. Because roof plank joint cracks run in the same direction as the two-dimensional slice of the vault used to simulate the problem, they could not be modeled as discrete cracks. Therefore, the effect of the roof plank joints in the concrete was averaged over the top of the vault and the roof was

S9409073.2

Figure 3.21. Features Within the Model of the Central Compliance Case (Case 1.0). Not drawn to scale.

Table 3.42. Detailed Parameter Inputs U

Material Description	Units	Grout	Asphalt Barrier	Corner Cracks in Asphalt	RCRA Cover	Backfill Soil	S
Particle Density	g/cm ³	2.620	2.720	2.720	2.720	2.720	2.720
Porosity, Theta E, T, D	-	3 @ 0.5781	3 @ 0.04	3 @ 0.04	3 @ 0.448	3 @ 0.371	3 @
Storativity	cm ⁻¹	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷	1.0 x
Saturated Hydraulic Conductivity (K _x , K _y)	cm/s	2 @ 1.00 x 10 ⁻¹⁰ 2 @ 1.50 x 10 ^{-8(b)} 2 @ 1.50 x 10 ^{-7(c)} 2 @ 1.50 x 10 ^{-6(d)}	2 @ 1.00 x 10 ⁻¹¹ 2 @ 3.00 x 10 ^{-5(a)} 2 @ 3.00 x 10 ^{-4(c)} 2 @ 3.00 x 10 ^{-2(d)}	2 @ 1.00 x 10 ⁻¹¹ 7.51 x 10 ⁻⁴ , 1.00 x 10 ⁻¹¹ (100 years ^(e)) 2 @ 3.00 x 10 ^{-3(c)} 2 @ 3.00 x 10 ^{-2(d)}	2 @ 1.00 x 10 ⁻⁷	2 @ 3.00 x 10 ⁻²	2 @
Residual Saturation $S_r = \frac{\theta_r}{\theta_s}$		0	0.1213	0.0 0.1213 (100 years)	0	0.1213	0.055
Van Genuchten n, alpha	none, cm ⁻¹	1.65, 1.08 x 10 ⁻⁵	2.08, 6.83 x 10 ⁻²	1.393, 7.61 x 10 ⁻⁶ 2.08, 6.83 x 10 ⁻² (100 years)	1.324, 5.39 x 10 ⁻⁴	2.08, 6.83 x 10 ⁻²	1.868,
Diffusion Coefficient D _{ab}	cm ² /s	5.78 x 10 ⁻⁷	1.00 x 10 ⁻¹⁰ 4.15 x 10 ^{-9(a)} 4.06 x 10 ^{-8(c)} 4.05 x 10 ^{-6(d)}	1.00 x 10 ⁻⁷ 4.05 x 10 ^{-7(c)} 4.05 x 10 ^{-6(d)}	2.50 x 10 ⁻⁵	2.50 x 10 ⁻⁵	2.50 x
Diffusion Parameter, a	1	1	1	1	0.005	0.005	0.005
Diffusion Parameter, b	0	0	0	0	10	10	10
Distribution Coefficient, Group No. 1a	ml/g	0	0	0	0	0	0
Distribution Coefficient, Group No. 2a	ml/g	2	0	0	0	0	0
Distribution Coefficient, Group No. 3c	ml/g	125	0	0	0	3.0	3.0

in Modeling the Central Compliance Case (Case 1.0)

rd ion y ce	Hanford Formation Gravel Sequence	Ringold Formation	Gravel Layer	Concrete in Vault Walls and Catch Basin	Top of Concrete Roof	Construction Joint Cracks in Concrete Walls	Concrete Roof	RCRA Flow Path and Floor Crack	Gravel in Catch Basin
	2.720	2.720	2.720	2.720	2.720	2.720	2.720	2.720	2.720
3	3 @ 0.3584	3 @ 0.4982	3 @ 0.518	3 @ 0.2258 3 @ 0.226574 ^(b) 3 @ 0.2274 ^(c)	3 @ 0.2258	3 @ 0.2258	3 @ 0.2258	3 @ 0.202	3 @ 0.518
	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}
10^{-3}	2 @ 2.73×10^{-4}	2 @ 2.42×10^{-6}	2 @ 1.85	2 @ 3.75×10^{-10} 2 @ $3.00 \times 10^{-5(b)}$ 2 @ $6.00 \times 10^{-5(c)}$	5.99×10^{-5} 1.00×10^{-11}	3.00×10^{-2} $3.75 \times 10^{-10(e)}$	2 @ 5.99×10^{-5}	2 @ 3.00×10^{-2}	2 @ 1.85
	0.05943	0.0568	2.703×10^{-2}	0.0 0.1213 ^(b)	0.1213	0.1213	0.1213	0.1213	0.02703
43	$1.613, 2.90 \times 10^{-2}$	$1.338, 1.76 \times 10^{-2}$	2.661, 3.5366	$1.393, 7.61 \times 10^{-6}$ $2.08, 6.83 \times 10^{-2(b)}$	$2.08, 6.83 \times 10^{-2}$	$2.08, 6.83 \times 10^{-2}$	$2.08, 6.83 \times 10^{-2}$	$2.08, 6.83 \times 10^{-2}$	2.661, 3.5366
	2.50×10^{-5}	2.50×10^{-5}	2.5×10^{-10}	5.00×10^{-8} $7.52 \times 10^{-8(b)}$ $1.50 \times 10^{-7(c)}$	6.18×10^{-8}	2.50×10^{-5}	6.18×10^{-8}	2.50×10^{-5}	1.00×10^{-9}
	0.005	0.005	1	1	1	0.005	1	0.005	1
	10	10	0	0	0	10	0	10	0
	0	0	0	0	0	0	0	0	0
	0	0	0	0	0	0	0	0	0
	3.0	3.0	0	0	0	0	0	0	0

Material Description	Units	Grout	Asphalt Barrier	Corner Cracks in Asphalt	RCRA Cover	Backfill Soil	Tal Hk For S Sec
Distribution Coefficient, Group No. 4a	ml/g	2625	0	0	0	0	0
Crack Size and Spacing ^(f)	as noted	NA	1 mm at 1 m ^(a) 1 cm at 1 m ^(c) Gone ^(d)	5 mm at 100 yr ^(g) 2 cm ^(c,g) Gone ^(g)	NA	NA	NA

(a)
5,000 years

(b)
5150 years

(c)
20,000 years

(d)
40,000 years

(e)
larger conductivity assigned in direction of crack, smaller conductivity in the direction perpendicular to

(f) Not actually a parameter entered in code. Information is reflected in other parameter values. A 1-mm weighting for the crack should be 2/1,000 and not 1/1,000, as has been applied throughout this analysis.

(g)
Cracks within a ~20-cm node.

Note: 3@ (or 2@) denotes three (or two) of the same value (e.g. K_x , K_y or Θ_E , Θ_T , Θ_D are the same).

e 3.42. (contd)

ord tion ly nce	Hanford Formation <u>Gravel Sequence</u>	Ringold Formation <u>Gravel Layer</u>	Concrete in Vault Walls and Catch Basin	Top of Concrete Roof	Construction Joint Cracks in Concrete Walls	Concrete Roof	RCRA Flow Path and Floor Crack	Gravel in Catch Basin
	0	0	0	0	0	0	0	0
	NA	NA	NA	1 mm at 1 m ^(b) 2 mm at 1 m ^(c)	NA	Full node 2 mm at 1 crack; see m (Root Figure 3.21 plan k)	Full node crack; see Figure 3.21	NA

crack

crack on a 1-m grid actually implies two 1-mm cracks on a 1-m² surface, and the associated equivalent property
1/1,000 weighting factor actually implies 0.5-mm cracks on a 1-m spacing.

given a hydraulic conductivity of 6×10^{-5} cm/s in all directions, simulating the presence of a 2-mm crack every meter of vault length. To prevent drainage from the intact diffusion barrier into the concrete (resulting from the linear averaging of conductivities being used), the top node of the concrete roof was given a hydraulic conductivity of 1×10^{-11} cm/s. This conductivity value matches the asphalt barrier property and was not changed during the simulation.

The remainder of the concrete vault was assumed to remain largely free of through-wall cracking over the first 5,150 years, after which generalized or "patterned" cracking was assumed to occur throughout the vault. The patterned cracking was implemented by changing the water retention properties of the concrete to those of the backfill soil and increasing the saturated hydraulic conductivity from 3.75×10^{-10} to 3.0×10^{-5} cm/s. This represents a 1-mm crack every meter (see Section 3.6.2.3). After 20,000 years, the concrete vault was assumed to have completed its degradation.

To simulate the presence of an HDPE flow path between the concrete wall and the asphalt barrier, the outside node of the vertical concrete wall was given water retention properties of the backfill soil and a hydraulic conductivity of 3×10^{-2} cm/s. The region of the gravel-filled catch basin was included as gravel. The sloped bottom of the catch basin and the presence of the leachate collection tank were neglected.

Grout. The diffusion coefficient for the grout was modeled as 5.78×10^{-7} cm²/s, with the driving force in the grout pore solution. This corresponds to 1×10^{-6} cm²/s if the driving force is defined in the bulk grout volume, and accounts for degradation of the grout diffusivity because of high-temperature curing. The grout was modeled with a saturated hydraulic conductivity of 1×10^{-10} cm/s for the first 5,150 years. The conductivity was increased to 1.5×10^{-8} cm/s at 5,150 years, 1.5×10^{-7} cm/s at 20,000 years, and 1.5×10^{-6} cm/s at 40,000 years. The sorption of contaminants within the grout was not altered with time.

Boundary Conditions. The boundary conditions were set initially and were not changed during the simulation. Zero gradient conditions were used on the left and right side of the problem for both flow and transport to represent a plane of symmetry between the two vaults of a pair (left boundary) and between pairs of vaults (right boundary). The top boundary was specified as a source of 0.1 cm/yr recharge and the concentration of contaminant was set equal to zero. At the bottom boundary (aquifer), the pressure was held at a constant -25 cm and the concentration gradient was set equal to zero.

Water Sources from Vapor Diffusion. Although the water condensing on the grout or concrete would evaporate from the surrounding soil, the water was modeled as a source of water within the problem and no water was removed from the soil. The diffusion of water vapor was modeled as water sources within selected cells of the problem.

The condensing water was introduced in the asphalt barrier cracks in the node closest to the concrete vault, along the bottom node of the concrete roof, and in the upper portion of the vault walls next to the grout. The sources on the vault walls extend 277 cm (9 ft) down the side of the vault and include the

initially uncontaminated grout cap, as well as 155 cm (5 ft) of contaminated grout. As described in Section 3.6.2.6 the sources at these points were ramped linearly between values calculated for specific time periods.

3.6.3.2 Delayed Cracking Case (Case 1.1)

The delayed cracking case was very similar to the central compliance case, except that the patterned cracking in the concrete and asphalt barrier was delayed from 5,000 years for the asphalt barrier and 5,150 years for the concrete until 10,000 years. The delay in cracking applies only to the patterned cracking occurring over the entire surface of the asphalt barrier and concrete vault. The cracks in the upper corners of the asphalt barrier still occurred at 100 years. The cracking associated with the construction joints in the walls and floor and the roof plank joints in the concrete roof were present initially.

The vapor diffusion water source in the asphalt barrier corner cracks matches that in the central compliance case. The first linear ramp of the vapor diffusion rate to the concrete vault occurred over 10,000 years instead of 5,000 years as in the central compliance case.

3.6.3.3 No HDPE Flowpath (Case 1.2)

The difference between this case and the central compliance case is that there was not an HDPE flow path in the outside node of the concrete walls and there was not a gravel region in the catch basin. These nodes were treated the same as the remainder of the concrete. However, several other differences that may be important in interpreting results are provided below.

Unlike the central compliance case, the concrete roof was treated the same as the remainder of the concrete. The initial water retention properties in the roof were those of concrete instead of backfill soil. The water retention properties were changed to those of the backfill soil, and increases in hydraulic conductivity and diffusivity were implemented at 5,000 years (not 5,150 years). After the water retention properties were changed, moisture drained from the concrete region. The hydraulic conductivity of the concrete roof was not increased to account for roof plank joints. The line of nodes along the top of the concrete roof does not have the reduced hydraulic conductivity values present in the central compliance case. The properties of the top node of concrete were changed over time in the same manner as the remainder of the concrete. The concrete vault walls did not have the construction joint cracks as in the central compliance case. The water vapor diffusion profile was ramped to its final value at 50,000 years instead of 40,000 years as in the central compliance case.

3.6.3.4 Composite Concrete Crack Model (Case 1.3)

The composite model case was the same as the central compliance case, except the composite model (see Appendix P, Section P.1.1) was used to represent the water retention properties for cracked concrete. The porosity, diffusivity, and hydraulic conductivity values were the same as in the central

compliance case. In addition, the treatment of cracking in the asphalt barrier and the rates of water vapor diffusion were the same as in the central compliance case.

3.6.4 Other Release Scenarios

In addition to the compliance case simulations for the 0.1-cm/yr groundwater pathway, several calculations were performed to investigate other potential pathways for exposure. These additional release scenarios are described below.

3.6.4.1 Radon Release Calculation

Radon is produced within the grout as part of the uranium-238 decay chain. Table 3.43 lists the nuclides of interest in the order of their appearance in the decay chain.

The small initial inventory of radium-226 causes the initial radon generation rate to be very small. However, the inventory of species higher in the decay chain (especially uranium-234) is expected to cause ingrowth of radium-226, increasing radon generation over time. To determine the radon generation rate as a function of time, the inventories and half-lives shown in Table 3.43 were used to calculate the activity of the species in the decay chain, including radium-226, as a function of time. From the activity of radium-226, the generation rate of radon-222 was estimated assuming an emanating power of 100%. The generation rate was then evaluated against performance objectives using a very simplistic calculation.

Table 3.43. Radionuclides Important to Radon Generation

Radionuclide ^(a)	Half-life	Initial Inventory ^(b) (Ci)
²³⁸ U	4.5×10^9 yr	9.69
²³⁴ U	2.5×10^5 yr	41.1
²³⁰ Th	7.5×10^4 yr	0.293
²²⁶ Ra	1.6×10^3 yr	3.73×10^{-4}
²²² Rn	3.8 day	none

(a) Short-lived species between uranium-238 and uranium-234 have been omitted.

(b) Values for radium-226 and thorium-230 are based on production estimates. Values for uranium-238 and uranium-234 are based on limited chemical analysis of wastes to be grouted. See Appendix E.

To estimate the release of radon from the grout, diffusive release is assumed to occur from all sides of the grout mass. Harris et al. (1992) summarized measurements of gaseous diffusion performed on concrete materials and concluded that for dry materials, diffusivities in the range 10^{-5} to 10^{-3} cm²/s are obtained. The diffusivity is very sensitive to the moisture content of the material, and diffusivities much less than this range would be expected for saturated material. Because of the high salt content of the grout and the high humidity of the subsurface environment, the grout is expected to remain saturated. However, to be conservative, the upper range diffusivity value of 1×10^{-3} cm²/s was used.

The diffusive release from the grout was modeled as a source within the grout equal to the maximum activity obtained for radium-226. The calculated diffusive flux of radon-222 was assumed to occur uniformly at all of the grout surfaces, leading to some conservatism regarding the edges and corners of the grout, where material was counted more than once in the simplified conceptualization of the source. After escaping the grout, the radon was assumed to immediately reach the top of the vault and begin diffusing through the cover materials.

For purposes of the calculation, the cover was treated as 5 m (16.4 ft) of dry backfill soil. In reality, the concrete, asphalt barrier, and RCRA cover may further delay the arrival of the radon, thus decreasing the flux at the ground surface. In addition, the Hanford barrier contains an asphalt layer and the soil in the barrier is likely to have higher moisture contents, thus decreasing the radon flux to the surface. However, treating the entire cover as backfill soil provided a conservative result. The effective diffusivity of radon in the backfill soil was selected as 4.5×10^{-2} cm²/s. This value is based on the diffusivity of radon in air and the void fraction of the backfill soil, neglecting the presence of the moisture. As a point of comparison, Hartley et al. (1985) provides an estimate of 2×10^{-2} cm²/s for radon diffusion in beach sand.

3.6.4.2 Upward Diffusion

The design goal of the Hanford barrier is to provide less than 0.05-cm/yr recharge to the soil column. In this performance assessment, the Hanford barrier is assumed to provide a recharge of 0.1 cm/yr to the soil column. However, it is possible that the recharge will be nearly zero. While 0.1 cm/yr is a conservative value for recharge in terms of the groundwater pathway, this amount of recharge tends to wash contaminants down from the surface, preventing contamination of the soil above the grout vault. This case was run to determine if upward diffusion of contaminants to the soil above the grout vault could be significant should the actual recharge rate be zero.

For this case, all properties were the same as those for the central sensitivity case described in Sections 3.6.1 and 3.6.5.1, except the recharge rate was set to zero. The boundary conditions were altered so at the top boundary the concentration gradient was set equal to zero, and at the bottom boundary the concentration was set equal to zero. The top boundary condition prevents contaminants from diffusing out of the top of the system. For purposes of evaluating the dose, the Hanford barrier itself was neglected, and the soil concentrations obtained at the top node of the backfill soil were used in the irrigated garden

scenario. If the Hanford barrier were considered, there would be additional attenuation of the concentrations. Because of the limited mobility in the absence of advection, the drinking-water pathway was not included.

The garden scenario has been used to convert calculated soil concentrations to doses, although it is recognized that applying of the garden scenario in this calculation is not realistic. Irrigation of a garden would provide recharge to the soil, and the effects of recharge would remove radionuclides from the top soil layers. However, using the soil concentrations in the garden scenario provides a conservatively high result. If the impact is within the performance objective, a more involved, less conservative analysis is not required.

3.6.4.3 Catastrophic Flood

Evidence of past ice ages and related flooding imply the likelihood of a catastrophic flood in the far future (see Sections 3.2.2.1, 3.2.4.2, and Appendix B). Such a flood could physically disturb the grouted waste and redistribute the waste near the ground surface. In the flood scenario, the flood was assumed to occur at 50,000 years. The entire inventory was then redistributed over the Hanford Site (an area of 1,450 km²) (560 mi²) to a depth of 10 m (33 ft). No credit was taken for depletion of the inventory due to transport during the first 50,000 years. Radioactive decay and ingrowth of daughter products was calculated for 50,000 years. The farm scenario was then used without the drinking-water pathway to calculate the dose.

3.6.4.4 High Recharge (Case 1.4)

High recharge at the Hanford Site is not expected. Even without the presence of the Hanford barrier, the average recharge is expected to be only 0.1 cm/yr. However, it is possible that over the time frames being analyzed, the climate could change significantly. To evaluate the effect on the results of higher recharge, a case using a recharge rate of 5 cm/yr was simulated. Because this case does not represent an expected condition, the results are not compared to performance objectives. The 5-cm/yr recharge was applied from the beginning of the simulation. However, it is expected that the time required for such a climate change to occur would be thousands or tens of thousands of years. Thus, applying the recharge initially is conservative from a time-of-arrival standpoint.

The high recharge case (Case 1.4) was similar to the central compliance case, with the most significant difference the recharge rate of 5.0 cm/yr instead of 0.1 cm/yr. However, there were several other differences between the two cases. Case 1.4 did not include the HDPE flow path along the outside of the concrete walls, the gravel zone in the catch basin, or the construction joint cracks in the concrete vault. The vault roof did not account for the presence of roof plank joints, and the line of low-conductivity nodes along the top of the concrete roof did not exist. When the first major change was made in the asphalt barrier and concrete hydraulic conductivity at about 5,000 years, the change in the concrete was implemented simultaneously with the asphalt change, rather than being delayed until 5,150 years as in the central compliance case. The porosity of the asphalt barrier was started at 0.04; then, as the barrier

cracked and degraded, the porosity stepped through values of 0.0402 at 5,000 years, 0.04162 at 20,000 years, and 0.202 at 40,000 years. The corner cracks in the asphalt were treated in a similar manner, except the values were slightly different (0.04405 at 100 years, 0.0562 at 20,000 years, 0.202 at 40,000 years). In the central compliance case, the porosity of the asphalt barrier and the corner crack region was held constant at 0.04. Finally, the final vapor diffusion water source was ramped linearly from its value at 20,000 years to its final value at 50,000 years. The central compliance case was ramped between the same values, but reached its final value at 40,000 years.

3.6.5 Design and Sensitivity Cases

This section describes the analyses performed to examine sensitivity to design features in the engineered system and the input parameters to the vadose zone transport calculations. In addition, the methodology used to determine sensitivity in the groundwater, and dosimetry analysis, is discussed. Finally, the sensitivity to inventory is discussed for the intruder and groundwater-related scenarios.

3.6.5.1 Central Sensitivity Case

The design and sensitivity cases were centered around the central sensitivity case (Case 2.0). Figure 3.22 illustrates the features included in the model of the engineered system. The detailed parameter inputs used in the base case are provided in Table 3.44. The central sensitivity case was developed prior to the compliance cases and represents a more simplified model of the system, especially with respect to the degradation of the engineered system over time. In the central sensitivity case, vertical and horizontal cracks existed initially in the asphalt and the concrete vault at the top corners in line with the edge of the grout. In addition, horizontal cracks were placed through the asphalt barrier and concrete vault in line with the bottom of the grout. In the compliance cases, the upper corner cracks did not penetrate the concrete vault and the location of the cracks in the asphalt barrier was in line with the corner of the concrete vault. The compliance cases did not use a crack in the bottom side of the asphalt barrier. The asphalt barrier cracks present in the central sensitivity case were larger than the corner cracks in the central compliance case. However, cracks that may exist in the concrete from the cracking of roof plank joints or construction joints were not included in the model. In addition, the effect of water vapor diffusion was not included in the sensitivity cases except where noted.

Diffusion in the asphalt barrier was modeled as if it occurred in the asphalt phase. For the modeling, the 0.162 fraction void space occupied by the asphalt was modeled as water filled so transport could be calculated. To prevent advection of the water used to represent the asphalt, the hydraulic conductivity of the asphalt barrier was set to a very low value (1×10^{-20} cm/s). The initial diffusivity value assigned to the asphalt barrier corresponded to that expected for an asphalt barrier. Over time, the diffusivity in the asphalt barrier was continually adjusted to account for biodegradation. At 90,000 years, the asphalt barrier water retention properties, hydraulic conductivity, and diffusivity were changed to match the backfill soil properties. The porosity of the barrier was increased from 0.162 to 0.202 and the pressure was set to

Figure 3.22. Features Within the Model of the Central Sensitivity Case (Case 2.0). Not drawn to scale.

)

)

)

Table 3.44. Detailed Parameter Inputs

Material Description	Units	Grout	Asphalt Barrier ^(a)	Cracks in Asphalt and Concrete
Particle Density	g/ml	2.620	2.720	2.720
Porosity, Theta E,T,D		0.5781	0.162 (.202) ^(a)	0.371
		0.5781	0.202 (.202) ^(a)	0.371
		0.5781	0.162 (.202) ^(a)	0.371
Storativity	cm ⁻¹	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷	1.0 x 10 ⁻⁷
Hydraulic Conductivity (K _x , K _y)	cm/s	2 @ 1.47 x 10 ⁻⁸	2 @ 1.00 x 10 ⁻²⁰ 2 @ 3.00 x 10 ⁻² 2 ^(a)	3.17 x 10 ⁻²² , 3.00 x 10 ⁻² (top corner) ^(b) 2 @ 3.00 x 10 ⁻² (bottom) 2 @ 3.00 x 10 ⁻² ^(a) (all cracks)
Residual Saturation $S_r = \frac{\theta_r}{\theta_s}$		0	0 .1213 ^(a)	.1213
Van Genuchten n, alpha	none, cm ⁻¹	1.65, 1.08 x 10 ⁻⁵	2.0, 1 x 10 ⁻⁷ 2.08, 6.83 x 10 ⁻² 2 ^(a)	2.08, 6.83 x 10 ⁻²
Diffusion Coefficient D _{ab}	cm ² /s	1.00 x 10 ⁻⁶	1.00 x 10 ⁻¹⁰ 2.50 x 10 ⁻⁵ ⁽¹⁾	2.50 x 10 ⁻⁵
Diffusion Parameter, a		1	1 0.005 ^(a)	0.005
Diffusion Parameter, b		0	0.0 10.0 ^(a)	10
Distribution Coefficient, Group No. 1a	ml/g	0	0	0
Distribution Coefficient, Group No. 2a	ml/g	2	0	0
Distribution Coefficient, Group No. 3c	ml/g	125	0	0
Distribution Coefficient, Group No. 4a	ml/g	2625	0	0

(a) Changes implemented at 90,000 years.

(b) Larger conductivity assigned in direction of crack, smaller conductivity in the direction perpendicular to crack.

Note: 2@ denotes (two of the same value [e.g. K_x, K_y are the same]).

Used in Modeling the Central Sensitivity Case (Case 2.0)

RCRA Cover	Backfill Soil	Hanford Formation Sandy Sequence	Hanford Formation Gravel Sequence	Ringold Formation	Gravel Layer Above Vault	Concrete Vault and Catch Basin
2.720	2.720	2.720	2.720	2.720	2.720	2.720
0.448	0.371	0.4203	0.3584	0.4982	0.518	0.2258
0.448	0.371	0.4203	0.3584	0.4982	0.518	0.2258
0.448	0.371	0.4203	0.3584	0.4982	0.518	0.2258
1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}	1.0×10^{-7}
2 @ 1.00×10^{-7}	2 @ 3.00×10^{-2}	2 @ 1.55×10^{-3}	2 @ 2.73×10^{-4}	2 @ 2.42×10^{-6}	2 @ 1.85	2 @ 3.75×10^{-10}
0	.1213	.0557	.05943	.0568	2.703×10^{-2}	0
$\frac{1.324, 5.39 \times 10^{-4}}{4}$	$2.08, 6.83 \times 10^{-2}$	1.868, 0.1943	$1.613, 2.90 \times 10^{-2}$	$1.338, 1.76 \times 10^{-2}$	2.661, 3.5366	$1.393, 7.61 \times 10^{-6}$
2.50×10^{-5}	2.50×10^{-5}	2.50×10^{-5}	2.50×10^{-5}	2.50×10^{-5}	2.50×10^{-10}	5.00×10^{-8}
0.005	0.005	0.005	0.005	0.005	1	1
10	10	10	10	10	0	0
0	0	0	0	0	0	0
0	0	0	0	0	0	0
0	3	3	3	3	0	0
0	0	0	0	0	0	0

-11.7 cm to achieve 0.162 volume fraction moisture. At this point, the moisture previously used to represent the asphalt phase was free to advect as water. This approach differs from that used in the compliance cases.

The diffusivity of species in the grout takes into account degradation of the grout that occurs during curing of the grout at elevated temperatures. Curing at elevated temperatures increases the diffusivity to values as high as $1 \times 10^{-6} \text{ cm}^2/\text{s}$ (based on the concentration driving force defined in the bulk grout). Sensitivity and design cases used this value directly, while it was adjusted for the compliance cases by multiplying by 0.5781 (grout porosity) to account for the increase in concentration resulting from tracking concentrations in the grout pore solution. Therefore, diffusive transport in the grout was slightly faster in the design and sensitivity cases than in the compliance cases.

3.6.5.2 Design Cases

Design cases were simulated to determine the relative importance of various features of the disposal system. The calculations were performed using the PORFLOW code and the same grid and material properties used in the central sensitivity case. The design cases consisted of a series of simulations, each with features of the engineered system either present or absent. The results were compared to the central sensitivity case to judge the effects of features of the engineered system. The design cases provided insight into the value of the barriers and an understanding of which features are important in the system. Table 3.45 provides the key elements for each of the design cases. In this table, the cases are listed starting with only the grout present and then adding engineered features to the system until the central sensitivity case is formulated.

Table 3.45. Features of the Design Cases

Design Case Identification	Description of Case
Grout in soil (Case 2.1A)	No engineered structures are present. The grout is placed directly in the backfill soil.
Grout in vault (Case 2.1B)	The grout is placed in a concrete vault, but there is no asphalt barrier. The gravel layer and the clay cap are both present. The concrete vault is cracked as in the central sensitivity case and the cracks are treated in the same manner. The only exception is that the conductivity assigned to cracks perpendicular to the crack direction in the upper corner cracks was $1.5 \times 10^{-8} \text{ cm/s}$ (matching the grout conductivity), rather than $3.2 \times 10^{-22} \text{ cm/s}$ in the central sensitivity case. Also, in the bottom concrete crack, the conductivity perpendicular to the crack direction was 1.5×10^{-8} compared to $3.00 \times 10^{-2} \text{ cm/s}$ in the central sensitivity case.

Table 3.45. (contd)

Design Case Identification	Description of Case
Barrier present (Case 2.1C)	The grout is placed in a concrete vault with an asphalt barrier and the clay cap over the vault pair. The gravel layer is not present. Both the asphalt barrier and the concrete vault are cracked as in the central sensitivity case and the cracks are treated as in the central sensitivity case. The initial condition for the moisture content in the backfill soil was 10 vol% rather than 5.6 vol% and the initial pressure head in the grout was -75 cm rather than approximately -338 cm. Upon degradation at 90,000 years, the asphalt region is set to a pressure head of -11.77 cm after the material properties are changed.
Gravel present (Case 2.1D)	The grout is placed in a concrete vault with an asphalt barrier and a gravel wedge overlying the barrier. This case differs from the central sensitivity case except the clay cap is not present, and when the asphalt barrier completely degrades at 90,000 years, the pressure in the barrier zone is not reset when the material properties are changed.
Central sensitivity case (Case 2.0)	This is the central sensitivity case used as the point of comparison for the sensitivity cases. This case includes all of the features of Case 2.1D plus the clay cap. After changing material properties of the asphalt barrier at 90,000 years, the pressure in the asphalt barrier region was set to -11.7 cm.

3.6.5.3 Sensitivity Cases

The sensitivity cases were derived from the central sensitivity case. Changes were made to various material property inputs to determine the effect of these inputs on the model. The sensitivity cases are numbered and organized by the area of the model being explored. Treatment of the transition of the asphalt barrier differed between some of the sensitivity cases and the central sensitivity case. The central sensitivity case set the pressure in the asphalt region to -11.77 cm after the asphalt barrier properties were altered to simulate complete degradation. Most sensitivity cases did not adjust this pressure and, unless noted otherwise, the pressure was not adjusted at 90,000 years in the sensitivity cases listed in Table 3.46.

Table 3.46. Features of the Sensitivity Cases

Sensitivity Case Identification	Description
<u>Grout</u>	
Case 2.2A	Identical to Case 2.0, the central sensitivity case, except the sorption of technetium-99 in the grout is neglected.
Case 2.2B	Saturated hydraulic conductivity of the grout is increased from 1×10^{-8} cm/s to 1×10^{-6} cm/s. At 90,000 years, the pressure in the barrier is set to -280 cm rather than -11.77 cm as in the central sensitivity case.
Case 2.2C	Saturated hydraulic conductivity of the grout is decreased from 1×10^{-8} cm/s to 1×10^{-9} cm/s.
Case 2.2D	The diffusivity within the grout is decreased by a factor of 100.
Case 2.2E	The initial condition within the grout is a pressure of -5,000 cm, compared to -338 cm in the base case.
<u>Asphalt Barrier</u>	
Case 2.3A	The water retention properties of the asphalt barrier are changed from those of the back-fill soil to concrete properties. The saturated hydraulic conductivity is increased from 1×10^{-20} cm/s to 1×10^{-11} cm/s. The 1×10^{-11} cm/s value is derived from nitrogen permeability measurements without correction for viscosity or surface effects. In addition, the conductivity in cracks perpendicular to crack direction was set to 3.2×10^{-12} cm/s in the top corner cracks, compared to 3.2×10^{-22} cm/s in the central sensitivity case.
Case 2.3B	The rate of biodegradation is increased from 1 cm/1,000 years to 2 cm/1,000 years. The barrier is completely degraded after 45,000 years.
Case 2.3C	This case compares only to Case 2.3D below. The difference between Cases 2.3C and 2.3D is that, in Case 2.3C, the porosity in the barrier is held constant at .202 (corresponding to the total asphalt plus air void fraction in the barrier), while in Case 2.3D, the porosity is held at 0.04 (corresponding to the maximum air void fraction in the barrier at construction). Cases 2.3C and 2.3D should not be compared to the central sensitivity case because they contain numerous differences from the central sensitivity case (see Appendix P).
Case 2.3D	This case is identical to Case 2.3C above, except the porosity of the barrier is 0.04 rather than 0.202.

Table 3.46. (contd)

Sensitivity Case Identification	Description
<u>Cracking</u>	
Case 2.4A	<p>This case used different crack locations and sizes than those used in the central sensitivity case. A schematic of the features included in the model is shown in Figure 3.23. The crack treatment has some similarities to the treatment of cracks in the compliance case. The upper corner cracks in the asphalt barrier are in line with the corner of the concrete rather than the grout. The crack widths are 1 cm in the top corner cracks and 0.5 in the lower crack. The concrete does not have major cracks in the upper corners. The 1-cm, upper corner cracks in the asphalt barrier are smaller than the 10-cm cracks in the central sensitivity case, but larger than the 0.5-cm crack in the central compliance case. The crack sizes are reflected by the hydraulic conductivities and diffusivities assigned to cells containing the cracks. All cracks are treated as having the porosity of the media through which they pass (0.202 in the asphalt barrier, .2258 in concrete). The vault walls each have four construction joint cracks (the compliance cases use five, while the central sensitivity has none). The sizes of the construction joint cracks are 0.1 cm at the top and bottom corner and 0.85 cm for the two middle cracks. These cracks are 100 times smaller than the cracks in the central compliance case, in which the cracks are represented as a full node of backfill soil. The vault roof region is assigned a conductivity of 6×10^{-5} cm/s to simulate the presence of 0.2-cm-wide roof plank joint cracks every meter of vault. As in the central compliance case, the roof is given the water retention properties of backfill soil. These roof plank joint cracks were not included in the central sensitivity case. Unlike the compliance cases, the increased conductivity from the roof plank joints is applied both in the vertical and horizontal directions. The top node of the concrete roof is assigned a vertical conductivity of 1×10^{-20} cm/s to prevent flow of moisture from the intact barrier above (the value used in the compliance case is 1×10^{-11} cm/s). In addition, the initial moisture content was set to 10% by volume in the soil rather than 5.6%.</p>
Case 2.4B	<p>This case was similar to Case 2.4A above, except the cracks in the asphalt barrier are represented by a full node of backfill soil in assigning the conductivity and diffusivity values. This treatment corresponds to crack widths at the upper vault corner of 18.9 cm (vertical crack) and 21.3 cm (horizontal crack). The cracks at the base of the vault are 10-cm wide.</p>
Case 2.4C	<p>This case is identical to the central sensitivity case, except the porosity, water retention, hydraulic conductivity, and diffusivity associated with gravel are assigned to the cracks passing through the asphalt barrier or concrete.</p>
Case 2.4D	<p>This case is the same as the central sensitivity case, except the upper corner cracks are eliminated.</p>

Table 3.46. (contd)

Sensitivity Case Identification	Description
Case 2.4E	This case is the same as the central sensitivity case, except the lower cracks in the asphalt barrier are not present. The lower crack in the concrete is still present but while the asphalt barrier is intact, it prevents flow out of the lower concrete crack.
Case 2.4F	This case is the same as the central sensitivity case, except there are no cracks in the asphalt or concrete.

Clay Cap/Recharge

Case 2.5A	The case is similar to the central sensitivity case, except the recharge rate is 5.0 cm/yr rather than 0.1 cm/yr and the clay cover is replaced by the backfill soil.
Case 2.5B	This case is the same as the central sensitivity case, except the recharge rate is 5.0 cm/yr.
Case 2.5C	This case is the same as Case 2.1D and is repeated because it makes a useful comparison. The case differs from the central sensitivity case in that the clay cap is not present.

Water Vapor Diffusion

Case 2.6A	This case is the same as the central sensitivity case, except a water source between 0.12 and 0.13 L/yr per meter of vault is introduced to each of the six major cracks (two at each upper corner and one at each lower corner). The water source is distributed evenly over five nodes starting at the grout surface (cold grout at upper corners) and extending outward through the crack for a distance of 83 to 89 cm, depending on the crack. The rate is calculated assuming a completely clear 91.4-cm-long, 10-cm-wide crack through the asphalt barrier.
-----------	--

Vadose Zone Eliminated

Case 2.6B	This case is the same as the central sensitivity case, except a flux plane is defined along the bottom of the asphalt and the material crossing this plane is immediately placed in the aquifer, thus eliminating much of the effect of the vadose zone. However, the vadose zone is still active in the problem and may have some influence on the diffusive and advective fluxes crossing the plane.
-----------	--

Figure 3.23. Features Within the Model of Sensitivity Case 2.4A. Case examines the sensitivity to cracking assumptions. Not drawn to scale.

3.6.5.4 Sensitivity in Groundwater Transport

Groundwater from the unconfined aquifer eventually enters and mixes in the Columbia River. However, this study and previous studies (U.S. DOE 1987; pages Q.33 to Q.38) have shown that exposures from consuming and using the river resource do not threaten the health and safety of the general population. Therefore, comments regarding the sensitivity of the groundwater model will focus on groundwater use and resource protection.

The opportunity for groundwater flow and transport processes to influence the results of this performance assessment is limited because the downgradient well is located only 100 m (330 ft) from the Grout Disposal Facility, and there is virtually no opportunity for the plume resulting from long-term release to disperse before reaching the well. Thus, point values of contaminant concentration in the groundwater 100 m (330 ft) downgradient of the Grout Disposal Facility were estimated to be identical to contaminant concentrations entering the aquifer from the vadose zone. However, point values of concentration were not used directly as estimates of water quality or indirectly in dose calculations in this performance assessment.

Simulation of groundwater flow and transport, when taken to include groundwater well hydraulics, is significant because of assumptions made here regarding how groundwater quality (well water concentration) is determined. These assumptions are based on how groundwater is used and protected by society, and upon recommendations of the DOE Performance Assessment Task Team. The task team recommended (Wood et al. 1992) that well drilling and completion practices in the region guide the development of logical scenarios for groundwater recovery and use. Furthermore, the task team recommended that current groundwater protection practices be used to define the water quality measured by monitoring methods for comparison to groundwater protection standards.

Monitoring wells at the Hanford Site currently screen a 6.1-m (20-ft) interval; 4.6 m (15 ft) of this screened interval is in the upper portion of the unconfined aquifer (Reynolds 1992). The wells are pumped and purged infrequently at a low rate to obtain representative samples for determining water quality. The wells draw water from at least the 4.6-m interval of the screen, and may draw water from below the partially penetrating well. To estimate the water quality of the monitoring well, contamination infiltrating into the aquifer from the Grout Disposal Facility was simply mixed into the upper 4.6-m interval of the unconfined aquifer. An estimation of the groundwater flux in this interval of aquifer beneath the Grout Disposal Facility depends upon the plume width in the groundwater system, the hydraulic gradient, and the saturated hydraulic conductivity. Scenarios involving low pumping rates use the above estimate of groundwater quality in assessing dose or groundwater protection.

The irrigated farm scenario involves the use of well water for the resident family and the 2-hectare farm. Records for Benton County (U.S. Bureau of the Census 1977) show that a typical family farm of this size uses 45 m³/d, and it is assumed that the well is completed in and draws its water from the uppermost aquifer unit, with sufficient yield to maintain this discharge. An area of uncertainty that exists but remains unquantified is that involving the well location and well screen position. For these analyses, no

attempt has been made to quantify the likelihood of placing a well and positioning a well screen to intercept the plume. However, it is clear that a well not placed downgradient of the Grout Disposal Facility, or in the immediate vicinity of the Grout Disposal Facility, would have a substantially lower potential of being contaminated by water originating in the Grout Disposal Facility.

Similarly, it has been assumed that water from the Grout Disposal Facility reaches the aquifer and is intercepted by the screened interval. However, there has been no attempt to quantify how other screen positions affect this assumption. For example, a partially penetrating well completed at the base of the aquifer or even in the middle of the aquifer might not draw any contaminated groundwater. If, during the drilling process, the unconfined aquifer does not provide sufficient yield, it is not uncommon for the well to be deepened to contact a confined aquifer unit exhibiting better yield. Of course, a well completed in a confined aquifer would not be contaminated by releases from the Grout Disposal Facility. Wells completed to greater depth in the unconfined aquifer (i.e., bottom and middle completion zones) are commonly constructed because they are less susceptible to problems of groundwater draw-down. Partially penetrating wells in the upper portion of an aquifer can be impacted, even dewatered entirely by draw-down. No attempt has been made to determine minimum or maximum concentrations that could be sampled in possible screened intervals. It was assumed that the screened interval does not dewater, and that it does intercept the Grout Disposal Facility release.

Based on the above references and discussion, groundwater use and resource protection have been assumed in this performance assessment to involve a groundwater well completed in the upper portion of the unconfined aquifer, i.e., a well partially penetrating the aquifer. This assumption is based on the current practice, in the vicinity of the Hanford Site, of using this type of well to produce groundwater for both residential use and monitoring purposes.

A well draws water from the three-dimensional region surrounding the screened interval; however, the contamination from the Grout Disposal Facility enters the aquifer from above and forms a lens of contaminated water at the water table. As a result, a considerable quantity of clean groundwater is mixed with contaminated groundwater as both are drawn into the well screen and pumped to the land surface through the well bore. This process has led to an estimate of well intercept for different aquifer situations (recharge rates) and well pumping rates (scenarios of water use or monitoring). The well intercept factor is defined as the ratio of infiltration from the Grout Disposal Facility to groundwater flux for a monitoring or low production well, and as the ratio of the intercepted portion of infiltration from the Grout Disposal Facility to pumping rate for the irrigated farm scenario. Based on this approach to analyzing the aquifer, uncertainty in groundwater flow and transport is best described in terms of the influence of different assumptions and parameters on the well intercept factor.

The potential significance of isotropic versus anisotropic hydraulic conductivity was also explored, and the importance of anisotropic conductivity confirmed, by modeling a 5-km² aquifer with the characteristic thickness, horizontal hydraulic conductivity, and anisotropy of the aquifer underlying the Grout Disposal Facility. The assignment of a relatively small vertical hydraulic conductivity in the anisotropic model (i.e., horizontal-to-vertical hydraulic conductivity ratio of 15 to 1) caused the well to draw its water

from an areally more extensive, but much shallower, portion of the aquifer. Comparisons to an isotropic model of the same aquifer, based on both SLAEMS and PORFLOW simulations, revealed the well intercept cross section was approximately doubled in the anisotropic case. A factor of two has been applied to correct the well intercept estimated by the isotropic SLAEMS model in the sensitivity cases described below. This study of isotropic versus anisotropic hydraulic conductivity could be viewed as a sensitivity study; however, it was done to determine the correct conceptual model. As a result, anisotropy has been incorporated into all results involving the 45-m³/d groundwater well.

The groundwater model and the resulting well intercept factor have been examined for sensitivity to three factors: 1) recharge rate, 2) pumping rate, and 3) number of vaults. Cases were examined using grout vault layouts consisting of 33, 4 and 1 vaults to determine the effect of total volume disposed on the well intercept factor. The well intercept factor was calculated in each case using either 0.1 cm/yr recharge or 5.0 cm/yr recharge, and either a pumping rate at the well of approximately zero (monitoring well) or 45 m³/day (irrigation well). The result of the analysis is a set of 12 well intercept factors (3 vault configurations x 2 well pumping rates x 2 recharge rates) that describe the sensitivity of the well intercept factor to these factors.

3.6.5.5 Sensitivity in Dosimetry

A sensitivity analysis was performed for dosimetry parameters in the irrigated farm, irrigated garden, and river scenarios to determine the influence of these parameters and their associated uncertainties on the dose estimates. The extent to which a parameter affects the total uncertainty in the dose estimate is a function of both the uncertainty in the parameter value and the overall importance of that parameter to the total dose estimate. For the groundwater and river scenarios, the sensitivity analysis was performed for unit concentrations of significant radionuclides in surfacewater or groundwater. Unit radionuclide concentrations were used in these cases to make the dosimetry sensitivity analysis independent of the groundwater transport sensitivity analysis, which was conducted separately.

The uncertainties associated with the external and internal dose conversion factors were not included in the analysis because these parameters are not variable in the computer program used to perform the calculations. The dose conversion factors used in the analysis are based on methods that have been generally adopted by most national and international agencies, although they may be associated with a substantial uncertainty themselves. The relative uncertainties associated with the internal dose factors for ingestion and inhalation have not been well characterized, and would be expected to vary depending on the radionuclide and exposure pathways being considered. The major sources of uncertainty in the estimates are individual variations in physiology and metabolism that influence uptake, transport, and clearance of materials from the body. Depending on the route of intake and the quantity of relevant exposure and metabolic data available, dose factors for individual radionuclides may be associated with ranges that span an order of magnitude to several (i.e., 3-4) orders of magnitude. For iodine-131, which is represented by a substantial body of clinical and experimental data, the upper 99% confidence limit for dose to the thyroids following ingestion is approximately three times the mean within a given age group (Dunning and Schwarz 1981). In contrast, the ingestion dose factors for transuranic radionuclides such as

plutonium-239, which are largely based on extrapolations from animal data, may vary by several orders of magnitude within a given population (Kocher et al. 1980). The uncertainty associated with external dose conversion factors is substantially smaller than that for internal dose conversion factors because the external dose conversion factors are more amenable to experimental measurement. Some variability would be expected, however, because of individual differences in physical characteristics of the general population. The analysis of dosimetry sensitivity in the irrigated farm and garden scenarios is presented in Section 4.2.3, and a detailed description of the methods and results appears in Appendix N.

In contrast to the sensitivity analysis for the groundwater scenarios, the sensitivity analysis for intruder scenarios included the effect of the initial grout inventory for all radionuclides simultaneously. For the intruder scenarios, uncertainties in the quantity of grout brought to the surface, the area over which the grout is distributed, and initial concentrations of significant radionuclides in the grout were also investigated. Results of this analysis are presented in Section 4.2.4.

3.6.5.6 Sensitivity in Inventory

In simulating release of radionuclides from the Grout Disposal Facility, initial dimensionless concentrations of 1.0 were used in the contaminated grout. After the simulations were completed, the dimensionless concentrations were converted to specific contaminant concentrations in downgradient groundwater wells. This approach is possible because the sorption model used in the performance assessment is linear. The insolubility of some species in the grout pore solution was incorporated with the sorption model. Because of this, the release of a contaminant to the groundwater was directly proportional to the inventory. If the number of vaults and site configuration are not changed, the concentration at a down-gradient well will also be proportional to the inventory. Inventory changes that alter the number of vaults and/or site configuration may not result in direct proportionality if the changes alter the well intercept factor for a groundwater well.

Groundwater Pathway. Possible sensitivity cases for the inventories of iodine-129, technetium-99, and neptunium-237 were identified in Table 8 of Appendix E. These radionuclides were selected because they were the three major contributors to dose impacts in all long-term simulations. Because of their mobility in the natural environment, iodine-129 and technetium-99 dominated the early response, while neptunium-237, because of its inventory and modest retardation in the waste form and natural environment, dominates the long-term response (e.g., for hundreds of thousands of years). The sensitivity cases for inventory are summarized in Table 3.47.

The sensitivity inventory values were obtained by using several different approaches to estimate the inventory for each radionuclide. Therefore, the selection of the sensitivity value was not based on the statistical uncertainty in the performance assessment inventory value. The performance assessment inventory values are based on the available analysis of wastes to be grouted. The Integrated Data Base (IDB) is used to track quantity and location of radioactive materials across the DOE complex and provides an alternate inventory value. The production values are based on a prediction of how much of the

Table 3.47. Inventory Sensitivity Cases for the Groundwater Pathway

Isotope	Performance Assessment Inventory (Ci) ^(a)	Basis	Sensitivity Analysis Inventory (Ci)	Basis
Iodine-129	14.6	Analysis ^(b)	46.4 34.2	Production ^(c) HDWEIS ^(d)
Technetium-99	6310	Analysis ^(b)	21,960 31,420	Production ^(c) IDB ^(e)
Neptunium-237	53.7	Analysis ^(b)	45.1 56.1	IDB ^(e) Production ^(c)

- (a) The values shown here represent the maximum inventory that can be disposed of under this performance assessment. If inventories greater than these are encountered, the impact will be evaluated and the performance assessment modified as appropriate.
- (b) Based on available analysis of wastes to be grouted.
- (c) Estimated based on application of ORIGEN2 data to the cesium-137 content of the waste.
- (d) Value used previously in the HDWEIS.
- (e) Based on the Integrated Data Base for tracking radioactive materials.

isotope would be present, based on the knowledge of the fission, activation, and decay reactions. Data from the ORIGEN2 code were used, along with the knowledge of the cesium-137 content of the waste, to make the estimate. The cesium-137 value used includes that currently present in the waste as well as that which will be or has been removed from the waste. Therefore, it represents a total production for the wastes planned for grout. It does not represent the entire site production for Hanford.

Intruder Scenarios. Sensitivity to inventory is different for the intruder scenarios than for the groundwater scenarios. The intruder dose depends on the concentration of radionuclides in the vault through which the intruder drills. Adding additional vaults to the disposal site does not change the intruder dose if the radionuclide concentration in the waste is not altered. For purposes of the performance assessment, the concentration obtained by evenly distributing the inventory over all vaults has been used. It is possible that some vaults could be higher than others in the concentration of important radionuclides. However, the extent of the potential variation is diminished somewhat because concentrated wastes are blended with dilute wastes to maintain the radionuclide heating load within set limits.

The important radionuclides for the intruder scenarios are different than those for the groundwater scenarios. Possible sensitivity cases for the inventory of the remaining radionuclides are identified in Table 8 of Appendix E. The inventory sensitivity cases for the intruder scenarios are summarized in Table 3.48.

The sensitivity case for cesium-137 was not identified in Appendix E but is provided here because some vaults may be filled with grout that is near the radionuclide heating limit. Of course, if some of the vaults are near the heating limit, other vaults with below-average inventory would have a lesser impact on an intruder.

The value chosen for tin-126 in the inventory was a conservative number based on the production expected for the amount of cesium-137 generated in the same waste. As before, cesium-137 that has been or will be removed has been accounted for in estimating this value. The only sensitivity case identified was the inventory based on the IDB. This value is more than an order of magnitude lower than the currently used value.

The various americium-241 sensitivity cases indicate that great uncertainty exists with this inventory. The highest inventory established as a sensitivity case is based on production and is a factor of

Table 3.48. Inventory Sensitivity Cases for the Intruder Scenarios

Isotope	Performance Assessment Inventory (Ci)	Basis	Sensitivity Inventories (Ci)	Basis
Cesium-137	1.61×10^7	Analysis ^(a)	4.54×10^7	Heat Limit
Tin-126	1.11×10^3	Production ^(b)	1.0×10^2	IDB ^(c)
Americium-241	2.84×10^3	Analysis ^(a)	1.7×10^3	Regression ^(d)
			5.37×10^4	IDB ^(c)
			1.0×10^5	Production ^(d)

(a) Based on available analysis of wastes to be grouted.

(b) Estimated based on application of ORIGEN2 data to the cesium-137 content of the waste.

(c) Based on the Integrated Data Base for tracking materials.

(d) Based on analysis using regression to describe waste volumes not otherwise adequately characterized (see Appendix E).

36 greater than the current inventory. In actuality, the inventory is limited to the 100-nCi/g TRU limit for near surface disposal (10 CFR 61.55). Wastes in individual tanks will be evaluated for their TRU content prior to grouting and will not be grouted if the waste exceeds 100 nCi/g. Based on an expected average waste density of 1.3 g/cm³, the inventory of americium-241 that would result in a 100-nCi/g waste concentration would be 1.6×10^4 Ci, a factor of 5.6 increase over the inventory value for this performance assessment.

The implications of these sensitivity inventories are discussed in Section 4.2.5.

3.6.6 Summary of Key Assumptions

Having presented the conceptual models for release and transport and described the details of the modeling approach for simulating the long-term performance of the Grout Disposal Facility, it is appropriate to summarize the key assumptions in the analysis that apply to the majority, if not all, cases. In a previous section under the topic of modeling approach, several assumptions were stated that apply to the entire analysis (i.e., a decoupled analysis is appropriate, porous media models apply throughout, deterministic models driven by parameter perturbations are an appropriate approach to sensitivity analysis), and these will not be revised. Key assumptions are listed below for source-term inventory and release; engineered system performance; unsaturated flow and transport; groundwater flow and transport; and environmental accumulation, exposure, and dose.

- Assumptions for source-term inventory and release:
 - The sampling and characterization of wastes in the double-shell tanks used in part to estimate waste characteristics and inventory are assumed to accurately reflect the contents of the waste tanks.
 - All vaults are assumed to fail simultaneously by scaling the results from a single vault to all 33 vaults. While unlikely in an absolute sense, this assumption is justified in light of the time frames of interest (e.g., thousands to tens of thousands of years), because failure of vaults and release of contamination are expected to occur over a relatively short period of time (e.g., several hundred years).
 - It is assumed that solubility does not govern the concentration of contamination in the pore solution of the grout. From laboratory leach tests, effective diffusivities were calculated for use in modeling transport in the grout. For the cases where contaminants were immobilized in the grout, leach test data were used to determine distribution coefficients and the release was modeled using a linear sorption isotherm model.

- For all species in the grout waste form, the molecular diffusivity in the pore solution is assumed to be $2.5 \times 10^{-5} \text{ cm}^2/\text{s}$. This parameter, along with tortuosity, was used to calculate retardation coefficients for species in the grout waste form. The tortuosity of the pores within the grout medium is assumed to be a property of the grout only because the size of grout pores will be large relative to contaminant molecules.
 - Contaminants are assumed to be transported under isothermal conditions in the grout and grout vaults, either by advection of pore solution or molecular diffusion within the pore solution. Compared with the long time frames simulated (e.g., tens of thousands of years), nonisothermal conditions are expected to occur over a relatively short time (e.g., less than 300 years).
 - The hydraulic properties of grout remain constant over specified lengths of time. Changes in the grout hydraulic properties to represent degradation are step functions. Grout is assumed to retain its unsaturated hydraulic characteristics and transport model parameters indefinitely. However, the saturated hydraulic conductivity of grout is assumed to be $1.5 \times 10^{-6} \text{ cm/s}$. This value is based on the assumed similarity between aged grout and the Ringold formation, which consists of well-rounded pebble-to cobble-size gravel with a matrix of sand, silt, and some clay. The Ringold formation varies from well-cemented conglomerate to open-work uncemented gravel.
- Assumptions for engineered system performance:
 - The van Genuchten-Mualem model used to describe water-retention and relative permeability relationships is applicable to the grout waste form, concrete vault, and the asphalt barrier. These relationships were developed for unsaturated porous media (soils). However, in this performance assessment, they are assumed to be applicable to low-porosity and low-permeability materials, fracture or cracked materials, and asphalt-coated materials that are not wetted by water.
 - The advection model can be applied to the asphalt phase of the asphalt barrier in the design and sensitivity cases as though it were water. Because the asphalt is hydrophobic and thus will repel water, this assumption is conservative. No measured hydraulic properties were available for asphalt. The approach was to use 16.2% or 20.2% porosity, depending on the case, with the unsaturated hydraulic characteristics of backfill soil.
 - Transport of contaminants through both the concrete vault and asphalt barrier is assumed to occur with no sorption. This assumption is conservative because sorption is expected to occur in the concrete structure. The sorption of species in backfill soil, and Hanford and Ringold formation sediments, was derived from existing literature or laboratory measurements.

- Step changes in hydraulic and transport properties for engineered materials are assumed to adequately represent the expected gradual degradation of structures. Step changes in hydraulic and transport properties were necessary to represent degradation in the numerical model of flow and transport through the Grout Disposal Facility.
- As materials in the engineered barriers degrade, their properties are assumed to degrade to those of other materials, selected to represent conditions worse than those expected (e.g., higher hydraulic conductivity). For example, the hydraulic properties of the asphalt barrier are changed to those of backfill soil when the barrier is completely biodegraded. This assumption is necessary because very little information exists about degradation of materials that will be used for the engineered barriers in the Grout Disposal Facility.
- Assumptions for unsaturated flow and transport:
 - Centerlines between vaults were used to define the two-dimensional domain evaluated with the unsaturated flow and transport model. The centerlines between vaults are assumed to be vertical no-flow boundaries by lines of symmetry. These lines of symmetry imply that infiltrating plumes from the different vaults move downward in a vertical soil column and do not intersect.
 - Transport properties within the unsaturated zone (distribution coefficients) are assumed to be constant in time and space. As waste solutions are released from the Grout Disposal Facility and enter the surrounding soil, they encounter a different geochemical environment, and transport properties will change as a function of the changing geochemical environment. However, values of distribution coefficient for individual transport groups were selected as conservative for the group, and, therefore, the transport properties are assumed to remain constant in the unsaturated zone. Most flow and transport models (including PORFLOW) are capable of handling only constant transport properties.
 - Dispersion was not modeled for transport in the unsaturated zone. No measurements of dispersion coefficients are reported for the unsaturated zone at the Hanford Site. Not accounting for dispersion in simulations is conservative in that higher peak concentrations are predicted.

- A recharge rate of 0.1 cm/yr is assumed to represent the base recharge for current climate conditions in the 200 East Area at the Hanford Site. The basis for this assumption was provided in Section 2.1.7.4 and Appendix F. Higher recharge (5 cm/yr) resulting from climate change and/or an ineffective protective barrier was investigated as a sensitivity case.
- Assumptions for groundwater flow and transport:
 - Dispersion was not modeled in groundwater transport. As with the unsaturated zone, no measurements of dispersion coefficients are reported for groundwater in the unconfined aquifer at the Hanford Site. Not accounting for dispersion in simulations is conservative in that higher peak concentrations are predicted.
 - The 4.6-m depth of the monitoring well screen is assumed to define the vertical extent of the cross section contaminated in the unconfined aquifer by waste from the unsaturated zone for dose calculations. The 4.6-m screened interval is assumed because it is consistent with well drilling and completion practices in the region and with current monitoring well practices at the Hanford Site.
- Assumptions for environmental accumulation, exposure, and dose:
 - The quantity of radionuclides entering the river annually through groundwater flow is assumed to be diluted by a volume of water corresponding to the annual average river flow rate at Priest Rapids Dam (Woodruff, Hanf, and Lundgren 1992). The assumption requires that radionuclides entering the river be completely mixed in the river volume at the receptor location. Whereas this treatment is not realistic for locations along the Hanford Reach of the river, it is reasonable for locations in the Tri-Cities that obtain their drinking water from the river. By the time the radionuclides reach McNary Dam, they would be completely mixed and substantially diluted by inflow from tributaries entering the river below Hanford.
 - Additional assumptions related to environmental accumulation and exposure calculations are presented throughout Appendix M, Scenario Descriptions.
 - It is assumed appropriate to calculate incremental doses from the use and consumption of contaminated water deriving from the Grout Disposal Facility, thus neglecting groundwater contamination associated with releases from other wastes and facilities in the vicinity of the Grout Disposal Facility.

3.7 Quality Assurance

Quality assurance performed as part of other grout performance assessments included activities that are part of the Hanford Environmental Dose Overview Panel (HEDOP), and activities at both PNL and WHC. This section describes the control of software and results used for modeling efforts in this performance assessment.

3.7.1 Hanford Environmental Dose Overview Panel (HEDOP)

The purpose of the HEDOP is threefold: to ensure that appropriate radiological and nonradiological environmental and health dose assessment methods are used at Hanford, to ensure that all Hanford-related environmental and health dose assessments are technically consistent, and to foster communication among the Hanford contractors regarding environmental and health dose assessments.

A major responsibility of HEDOP is to establish and maintain a list of HEDOP reviewers who perform reviews of completed environmental pathway and health dose assessments. HEDOP reviewers conduct these reviews to ensure appropriate methods are used, to assure consistency in the technical approach used to perform calculations, and to promote communication among DOE contractors performing these analyses. The HEDOP review is an overview, as implied by the Panel name, although technical issues may also be addressed as part of the review. Indeed, separate from their role as HEDOP reviewer, the same individual may be asked to perform a peer or technical review of the reported analyses. All dose calculations appearing in this performance assessment have been reviewed and approved for publication by a HEDOP reviewer.

3.7.2 Westinghouse Hanford Company Quality Assurance

Contributors from WHC for this performance assessment conducted activities of the project under the guidance of the provisions of the American Society of Mechanical Engineers (ASME) Nuclear Quality Assurance (NQA)-I Program Requirements for Nuclear Facilities (ANSI/ASME 1989), as required by DOE Order 5820.2A (U.S. DOE 1988a). The manner in which the first 18 basic elements of NQA-1 are implemented in the Grout Program is documented in the *Hanford Site Grout Facilities Quality Assurance Program Plan* (Wood et al. 1992). There are no implementing procedures specific to the Grout Technology Project. Instead, the procedures of the WHC *Quality Assurance Manual* [WHC-CM-4-2] (WHC 1992b) were used. These are indexed corresponding to NQA-1.

For this performance assessment, basic item 19 of the Westinghouse Quality Assurance Program (software quality assurance requirement) was implemented through the use of the document *Software Practices* [WHC-CM-3-10] (WHC 1993b) and Section 2.1 of *Standard Engineering Practices* [WHC-CM-6-1 (WHC 1992c)]. The code used (i.e., PORFLOW) was under configuration control and went through a verification process [see Section 3.5.2.3, Appendix H, and Piepho et al. (1994)]. The input and output of all simulations used in this report were reviewed by a second party.

3.7.3 Pacific Northwest Laboratory Quality Assurance

The grout performance assessment work conducted by PNL was performed in accordance with the appropriate portions of PNL's Quality Assurance (QA) Program. The PNL QA program conforms to NQA-1, *Quality Assurance Program Requirements for Nuclear Facilities*, as interpreted in Parts 1 and 3 of PNL-MA-70, *Quality Assurance Manual*. Part 3 of the manual is a set of administrative procedures that define how the various requirements of NQA-1 are implemented. The administrative procedures define controls, policies, and established methods for managing and conducting all aspects of work that affect quality.

For experimental studies at PNL supporting this performance assessment, all phases of the work were performed in accordance with the QA program. The QA program administrative procedures have been established to control all aspects of work that can affect quality. Some of the controls include the following:

- indoctrination, training, and qualification of staff
- control of supplies and services
- control of test materials
- preparation and control of test plans and procedures
- control and calibration of measuring and test equipment
- control of the experimental design
- performance, documentation, and evaluation of test results, and
- identification and correction of conditions adverse to quality.

Computer codes used for the performance assessment are documented, tested, and reviewed in accordance with software control procedures established as part of the overall QA program. These software control procedures have been structured to address the requirements of ANSI/ASME NQA-1, Basic Requirements 3, and Supplement 3S-1, Supplementary Requirements for Design Control. The procedures cover all aspects of code development and usage, including the following:

- identifying, reviewing, and controlling inputs used for code development or code acquisition
- controlling the code development process, including a final development review

- controlling verification, validation, and conversion testing activities, and
- managing the configuration of established codes.

A key aspect of the QA program involves the technical and peer reviews of procedures, test plans, data, calculations, and other test results. These reviews help to ensure that the results are complete, correct, and consistent with the supporting records. The reviews range from verifying that calculations or data reduction have been performed correctly to the evaluation of test methodology, as described in a proposed test plan. These reviews are performed for essentially all aspects of work supporting the performance assessment.

Periodic, comprehensive audits are performed by QA auditors to ensure that all applicable elements of the QA program are being effectively implemented. In addition, a QA engineer assigned to the program performs routine reviews and evaluations to ensure that the QA program is being effectively implemented. The QA engineer periodically evaluates data to ensure it is fully supported by complete and correct records. In addition, evaluations may include test activities in progress to ensure that the activities are being performed in accordance with requirements of the QA program and the technical planning documents.

Records generated from all activities are indexed and managed in accordance with QA program requirements. Records holding facilities are used for long-term records retention and storage.

3.7.4 Performance Assessment Technical Reviews

Over the course of developing this performance assessment, the program has conducted a number of independent technical reviews; one on the performance assessment methodology and several on the evolving performance assessment document itself. These reviews are listed below. In addition, numerous internal PNL and WHC technical reviews have been conducted during the performance assessment preparation and revision. The recommendations from these internal and external reviews have been incorporated, as appropriate, into the performance assessment process and documentation.

In October 1988, PNL convened a 5-member panel drawn from academia to review the performance assessment methodology being proposed and experimental work underway at the time in support of the performance assessment and disposal system design. A third-party technical review of the grout performance assessment in progress was conducted in July 1989 (Advanced Sciences, Inc. 1989). Another third-party technical review was conducted in December 1989 to confirm the validity of the "water vapor return phenomenon."

DOE Order 5820.2A (U.S. DOE 1988a) includes provisions for a Peer Review Panel (PRP) composed of DOE, contractor, and other specialists in performance assessments. The PRP is charged with assuring consistency and technical quality of performance assessments prepared across the DOE complex. This PRP conducted a preliminary review of the PA in progress in May 1989 and a detailed review of the

performance assessment documentation during 1991. Based on that review, the PRP requested a revision of the grout performance assessment to address their concerns. This 1993 revision of the performance assessment addresses those concerns.

To assist in preparing the 1993 revision of the grout performance assessment, a Steering Committee of senior PNL and WHC technical staff was formed to help guide the revision process. The Steering Committee is chartered with providing review and guidance on specific issues as they arise in the revision process and with providing a final technical review of the performance assessment document. Resumes of the Steering Committee members are included in Chapter 6 of this document.

4.0 Results of Analysis

This chapter presents the results of the analyses conducted for this performance assessment. Section 4.1 presents the results of the analyses of 1) exposures due to flow and transport of radionuclides to the groundwater and to the Columbia River, 2) exposures resulting from inadvertent intrusion into the grout vaults, and 3) exposures from other potential natural processes or events. Section 4.2 examines the sensitivities and uncertainties in the results. Section 4.3 provides an integration and interpretation of the results. In Chapter 5, the results of the analyses are compared to the performance objectives outlined in Chapter 1.

4.1 Results of Exposure Pathways Analyses

This section presents the results of analyses conducted to evaluate the performance of the engineered disposal system for comparison with the performance objectives. First, intermediate results for modeling the flow and transport of contaminants through the engineered disposal system and the soil column to the groundwater are presented. Second, the impacts of groundwater contamination are discussed in terms of the exposures from use of contaminated well water or Columbia River water. Third, exposures resulting from inadvertent intrusion into the grout vaults are presented. Finally, exposures from other potential natural processes or events are discussed.

Because of uncertainties involved in predicting long-term changes of properties in the engineered features of the disposal system, a series of simulations were completed that incorporated staged degradation of the engineered structure based on the conceptual model of the disposed system. The simulations presented here represent the best effort to date to predict the very long-term performance of the grout and engineered system. These cases were selected to compare to the performance objectives and are referred to as compliance cases. Several similar cases have been simulated with slightly different approaches to determine the effects of the different approaches. Currently, the knowledge of long-term degradation is not sufficient to select a single staged-degradation simulation as a best estimate case.

The compliance cases presented here are described in detail in Chapter 3. Because of the amount of detail required to completely describe a simulation, only the primary differences between the different simulations are discussed here. In this performance assessment, Case 1.0 is the central compliance case, in that all other cases involving staged degradation represent parameter changes from this case. Table 4.1 summarizes the differences among the cases. The reader may wish to review the conceptual model description for Case 1.0 in Chapter 3 before continuing here (see Section 3.6.2).

Table 4.1. Differences in Compliance Case Simulations

Case	Model for Concrete Crack Hydraulic Properties	Liner/Catch Basin Structure	Timing of General Concrete/Asphalt Cracking (yr)
1.0 - Central compliance	Backfill Soil	Included	5,150/5,000
1.1 - Delayed cracking	Backfill Soil	Included	10,000/10,000 ^(a)
1.2 ^(b) - No HDPE flow path	Backfill Soil	<i>Neglected</i>	5,000/5,000
1.3 - Composite model ^(c)	<i>Composite Model</i>	Included	5,150/5,000

(a) Items in italics indicate changes from central Case 1.0.

(b) Case 1.2 had several additional differences (see Section 3.6.5.3).

(c) For a description of the composite model, see Appendix P, Section P.1.1.

4.1.1 Intermediate Transport Results for Groundwater Pathway

This section provides the results of transport from the engineered disposal system to the groundwater. The discussion is divided between results of transport in the vadose zone and results of release into the aquifer.

4.1.1.1 Vadose Zone Results

This section presents the moisture content, advective velocities, and contaminant concentrations within the soil column. The results focus on Case 1.0, the central compliance case considered.

The distribution and movement of moisture within the disposal system are calculated throughout the simulation as the properties of the engineered system are changed in response to assumed degradation processes. A plot of the moisture content (volume percent moisture) within the vadose zone at 10,000 years is shown in Figure 4.1. A contour plot of the corresponding magnitude of horizontal and vertical Darcy velocities is shown in Figure 4.2A and 4.2B, respectively. Contour plots for additional times are provided in Appendix P. The moisture content contours within the system change very little between 1,000 and 10,000 years.

Plots of the relative concentration contours for transport group 1A (iodine-129) are shown in Figures 4.3 (1,000 years), 4.4 (10,000 years), and 4.5 (50,000 years). The contour plot at 50,000 years is close to the time of peak dose from all radionuclides of 48,400 years (as determined from the scenario that uses groundwater to irrigate a family farm). In these plots, a concentration of 1.0 is the initial

Figure 4.1. Case 1.0: Moisture Content Contours for Vadose Zone at 10,000 Years
(numbers at right are volume fraction moisture and indicate contours shown)

Figure 4.2A. Case 1:0, Central Compliance Case: Horizontal Darcy Velocity Contours Within Vadose Zone at 10,000 Years. Darcy velocity in m/yr. (Numbers at right indicate the contours shown.)

Figure 4.2B. Case 1:0, Central Compliance Case: Vertical Darcy Velocity Contours Within Vadose Zone at 10,000 Years. Darcy velocity in m/yr. (Numbers at right indicate the contours shown.)

Figure 4.3. Relative Concentration Contours for Iodine-129 or Other Species in Transport Group 1A at 1,000 Years in Case 1.0. Does not include radioactive decay. (Numbers at right indicate contours shown.)

Figure 4.4. Relative Concentration Contours for Iodine-129 at 10,000 Years in Case 1.0. Does not include radioactive decay. (Numbers at right indicate contours shown.)

Figure 4.5. Relative Concentration Contours for Iodine-129 at 50,000 Years in Case 1.0. Does not include radioactive decay. (Numbers at right indicate contours shown.)

condition for the grout region. Iodine-129 is the most mobile radionuclide within the grout and is modeled without sorption anywhere in the engineered system or environment.

When interpreting the concentration contours, it should be noted that the plot is of concentration in the liquid phase (calculated using liquid volume, not total volume). Therefore, in comparing regions with similar concentration values, regions with a higher moisture content will contain a larger inventory than regions with a low moisture content.

Figure 4.3 shows the concentration contours at 1,000 years. As can be seen, the contaminant has not yet reached the aquifer in any appreciable amount. Because of the recharge from the top of the system, the contaminant does not migrate upward by diffusion. The primary movement of contaminant away from the vault is occurring along the sides of the vault. The lower flow through the engineered system causes the concentration profiles in the soil to dip upward underneath the vault. Concentrations within the grout decreased partially because of release from the engineered system, and partially because of transport of contaminants from the grout into the cold grout and the concrete of the vault and catch basin.

Figure 4.4 shows the concentration profile at 10,000 years. The concentrations within the soil column have increased significantly. The greater release is due to substantial increases in the hydraulic conductivity of the grout and asphalt barrier at 5,000 years and an increase in hydraulic conductivity of the concrete at 5,150 years. In addition, the water retention properties for concrete are changed to those of backfill soil at 5,150 years, resulting in drainage of moisture from the concrete. These changes simulate the onset of generalized cracking in the asphalt barrier, concrete vault, and grout (see Section 3.6.2 and 3.6.3.1). These changes increase the amount of advection occurring directly through the engineered system. The highest concentrations in the soil column are located directly beneath the grout vault. However, despite the greater concentrations in the soil column, less than 1.5% of the total inventory has been released to the aquifer. The rate of release to the groundwater increases after 10,000 years as the higher concentration profiles reach the bottom of the vadose zone.

Figure 4.5 shows the concentration profiles for iodine-129 at 50,000 years. The final steps in the degradation of the asphalt barrier and grout occurred at 40,000 years. The contour plot represents the system near the time of the peak dose from all radionuclides in the farm scenario and, for the iodine-129 dose, just after the final peak. After this time, the dose from iodine-129 declines. Note that the source in the engineered system has been significantly depleted.

4.1.1.2 Release to Groundwater

This section provides intermediate results of the fractional release of the inventory and the groundwater concentrations for the central compliance case (Case 1.0).

The fractional release of the inventory for Case 1.0 is shown in Figure 4.6. This figure does not account for the inventory of individual species within each transport group, and does not include the

Figure 4.6. Fractional Release to the Groundwater Per Year for Case 1.0. Effects of radioactive decay are not included. Curves correspond to results for transport groupings: iodine-129, group 1A; technetium-99, group 2A; neptunium-237, group 3C; uranium-238, group 4A.

effects of radioactive decay. It illustrates the fraction of the initial grout inventory transported from the vadose zone to the aquifer in a given year. The curve for iodine-129 applies to any species in transport group 1A.^(a) Similarly, the curves for technetium-99, neptunium-237, or uranium-238 would be applicable to other contaminants whose transport properties place them in transport groups 2A, 3C, or 4A, respectively.

The releases to the groundwater are extremely small prior to 2,000 years because of the time required for contaminants to migrate from the engineered system to the aquifer. Between 2,000 and 5,000 years, the release of iodine-129 and technetium-99 increases as the release from corner cracks in the asphalt barrier of a grout vault reaches the groundwater. Following significant degradation of the asphalt barrier, concrete vault, and grout at 5,000 years, the rate of release of technetium-99 and iodine-129 to the groundwater increases sharply at about 7,000 years. At 10,000 years, the release to the aquifer of species in groups 3C and 4A are extremely small because of the sorption behavior in the soil and grout. After 100,000 years, the rate of technetium-99 and iodine-129 release to the aquifer decreases as the inventory becomes depleted. The initial release behavior of group 4A parallels the release curves of groups 1A and

(a) The term "transport group" refers to a pair of specific distribution coefficients in the grout (specified by the number) and soil (specified by the letter). All species within a transport group are modeled using the same distribution coefficients in these regions. See Section 3.3.

2A, except that the fractional release is much lower because of sorption in the grout. After reaching a maximum release rate, the fractional release of group 4A forms a plateau that decreases very slowly because of strong sorption in the grout. Group 3C includes sorption in both the grout and soil column, resulting in a delayed arrival (primarily due to soil column sorption) and a much lower and broader peak (primarily due to sorption in grout).

Figure 4.6 illustrates the effect of sorption in the grout and soil. The primary effect of increased sorption in the grout is to shift the fractional release curve vertically downward. This shift is approximately one order of magnitude for technetium-99 (transport group 2A) and over four orders of magnitude for uranium-238 (transport group 4A). This vertical shift is most straightforward in the first few thousand years while the inventory of the less sorbed species has not been significantly depleted. The effect of sorption in the soil column can be seen by examining the curve for neptunium-237 (transport group 3C), which is modeled with sorption in both the grout and soil. In this case, the initial arrival time of the contaminant is delayed significantly and the curve is smoothed and spread over time, providing an additional decrease in the magnitude of the peak release to the aquifer.

The predicted concentrations of iodine-129, technetium-99, and neptunium-237 in the groundwater (assuming a 4.6-m mixing depth) are shown in Figure 4.7 as a function of time. These concentrations are determined using the fractional release information determined above for each transport grouping. Other factors contributing to the calculation include the inventory for each species, the recharge from the site, the groundwater flow, the travel time to the well, radioactive decay, and the 4.6-m mixing depth in the groundwater. This calculation is described in Section 3.5.4.

Figure 4.7. Concentrations in Groundwater for Key Radionuclides. Assumed mixing depth 4.6 m.

4.1.2 Dose Results for Groundwater Pathway

This section provides the doses calculated for the selected groundwater pathway exposure scenarios. Doses for all of the compliance cases are presented and compared to performance objectives. Additional detail in terms of the breakdown of the dose by radionuclide is provided for the central compliance case (Case 1.0). A summary of doses for the compliance cases is provided in Table 4.2.

Table 4.2. Summary of Dose Results for Compliance Cases

Scenario	Performance Objective	Dose Result by Case ^(a) (mrem/yr)			
		1.0	1.1	1.2	1.3
Irrigated Farm					
1,000 years ^(b)	25 mrem/yr	<0.01	<0.01	<0.01	<0.01
10,000 years ^(c)	25 mrem/yr	3.0	0.28	5.2	0.84
Maximum Dose ^(d)	NA	18	18	20	24
Garden					
1,000 years	25 mrem/yr	<0.01	<0.01	<0.01	<0.01
10,000 years	25 mrem/yr	4.8	0.47	8.2	1.4
Maximum Dose ^(d)	NA	26	26	28	35
Groundwater Protection (drinking water)					
1,000 years	4 mrem/yr	<0.01	<0.01	<0.01	<0.01
10,000 years	4 mrem/yr	4.1	0.42	6.9	1.2
Maximum Dose ^(d)	NA	19	20	20	26
Community Well ^(e)		Cumulative Dose (person-rem/yr)			
Maximum Dose ^(d)	500-person-rem/yr	2.1	2.0	2.2	2.8
River ^(f)					
Maximum Dose ^(d)	500-person-rem/yr	0.038	0.039	0.042	0.052

(a) Refer to Table 4.1 or Chapter 3 for description of cases.

(b) 1,000 years corresponds to regulatory performance objective from DOE-RL 5820.2A.

(c) 10,000 years corresponds to the programmatic performance objective.

(d) In all cases the maximum dose occurs at approximately 50,000 years.

(e) The community well serves 80 people.

(f) The downstream population in the river scenario is 5×10^6 people.

4.1.2.1 All Pathways, Maximum Individual

Irrigated Farm Scenario. The farm scenario (see Section 3.2.4.1) includes the all-pathways exposure from the use of downgradient well water for drinking, irrigating, and watering livestock. The farm scenario dose for Case 1.0, along with the breakdown of the radionuclides that contribute to the dose, are shown in Figure 4.8. Due to the scale selected for dose in Figure 4.8, the dose is not visible until after 5,000 years. However, doses exceeding 1×10^{-6} mrem/yr are calculated after 2,000 years and doses exceeding 0.01 mrem/yr are calculated after 3,500 years. Similar results are obtained for other groundwater-related scenarios in compliance case simulations. Included in Figure 4.8 are shaded regions illustrating the regions that would not meet the 1,000-year 25-mrem/yr performance objective from DOE-RL Order 5820.2A (labeled "regulatory performance objective"), as well as the more conservative 10,000-year time frame adopted by the program as a design goal and used in this performance assessment as a performance objective (labeled "programmatic performance objective"). As the figure shows, the results fall outside of the shaded regions, indicating that the performance objectives for this scenario are met. The peak dose of 17.5 mrem/yr occurs at 48,400 years. Therefore, the dose for the irrigated farm scenario is below 25 mrem/yr for all time. At the time of the peak, 77% of the dose is attributed to technetium-99, with the remainder from iodine-129. The technetium-99 exposure occurs 80% through the ingestion pathway and 20% through drinking water. The iodine dose occurs 62% through drinking water and 38% through ingestion. Other pathways and radionuclides are much less significant.

Figure 4.8. Case 1.0, Central Compliance Case: Breakdown of Farm Scenario Dose by Radionuclide. Shaded areas indicate where performance objectives would not be met.

The farm scenario doses for the four compliance cases are shown in Figure 4.9. All cases are within the 10,000-year, 25-mrem/yr performance objective. In fact, the farm scenario dose never exceeds 25 mrem/yr at any time. The dose results for the different compliance cases are essentially similar, although there are minor differences between the curves. The discussion below identifies these differences.

Prior to 5,000 years, the doses for all cases are fairly low because of the travel time to the aquifer and the limited cracking at the upper corners of the asphalt barrier vaults. The doses for Case 1.2 [no high-density polyethylene (HDPE) flow path] are slightly lower prior to 5,000 years, possibly because other compliance cases experience increased diffusion through the RCRA structure to the corner cracks. Otherwise all the cases are nearly identical until 5,000 years.

At or near 5,000 years, Cases 1.0, 1.2, and 1.3 are modeled as experiencing generalized cracking of the grout, concrete, and asphalt barrier. The effects of these cracks are implemented in the model as significant increases in the hydraulic conductivity of the grout, the concrete and the asphalt barrier, and in changes in the water retention properties for the concrete. These changes result in significant increases in releases from the engineered system for all cases. In Case 1.1 the changes in the asphalt barrier and concrete are not implemented until 10,000 years, a treatment that substantially decreases the doses prior to 10,000 years.

Figure 4.9. Compliance Cases: Farm Scenario Dose. Shaded regions indicate where performance objectives would not be met.

In the time period of 5,000 to 20,000 years, the curves in Figure 4.9 diverge. During this period Case 1.2 reaches the highest dose of the compliance cases. In Case 1.2, the concrete roof changes water retention properties from concrete to backfill soil at 5,000 years and the pore water drains from this region. All other cases in Figure 4.9 initially use the water retention properties of backfill soil in the concrete roof to avoid this drainage of pore water. Both Cases 1.0 and 1.2 experience drainage from the sides and bottom of the vault and catch basin concrete at 5,150 and 5,000 years, respectively. However, because there is not a catch basin cavity in Case 1.2, the amount of moisture draining is more than in Case 1.0. In addition, there are low-conductivity cells in the top of the concrete in Cases 1.0, 1.1, and 1.3 that are not present in Case 1.2. The presence of these cells may also contribute to the higher dose for Case 1.2 in the 5,000- to 20,000-year time frame.

Case 1.3 uses the composite model for unsaturated hydraulics of the cracked concrete on the sides and bottom of the engineered system. Use of the composite model prevents the drainage of pore water from the concrete as seen in other cases. The rise in dose after 5,000 years in Case 1.3 is not as rapid as that in Cases 1.0 and 1.2. The rise in dose in Case 1.1 is delayed until the changes in the concrete and asphalt barrier are introduced at 10,000 years. At 10,000 years the dose seen in Case 1.1 resulting from release through the corner cracks is only 0.3 mrem/yr.

Degradation of the system is modeled as being completed at 40,000 years in all cases. At times greater than 40,000 years, the initial delay in degradation is no longer evident in the results, and Cases 1.0 and 1.1 are nearly identical. The highest peak dose is obtained in Case 1.3 (24 mrem/yr versus 18 mrem/yr for Case 1.0). The release modeled in Case 1.3 appears to be greater than that for other cases after 40,000 years, probably because of the composite model used for the concrete cracking. The higher release causes the curve to dip low at about 100,000 years as the technetium-99 is depleted prior to the arrival of the dose from neptunium-237. In addition, the final dose from neptunium-237 is slightly higher in Case 1.3 than in other cases. Case 1.2 shows a greater release after 100,000 years than Cases 1.0 and 1.1. This difference may be due to the absence of a Resource Conservation and Recovery Act (RCRA) liner and catch basin structure; it also may be due to the low conductivity cells included in the top of the concrete barrier, or to other differences.

Irrigated Garden Scenario. The garden scenario (see Section 3.2.4.1) is very similar to the farm scenario in that it is an all-pathways scenario for a maximum individual and is compared to the 25-mrem/yr performance objective. However, the garden scenario excludes the ingestion of animal products, a pathway included in the farm scenario. Also, the volume of water withdrawn from the well is less in the garden scenario, resulting in less mixing with uncontaminated water in the well intercept and higher concentrations in the water used in the scenario. The doses calculated for the garden scenario for Case 1.0 are shown in Figure 4.10 and include a breakdown by radionuclide. The boxes in the upper left of the figure show the 1,000-year regulatory performance objective period and the 10,000-year programmatic performance objective. Both of these objectives are met with the maximum dose over the first 10,000 years of 4.8 mrem/yr occurring at the end of the period. The increase in dose in the garden scenario over the farm scenario is due primarily to the increase in concentration that results when less water

Figure 4.10. Case 1.0, Central Compliance Case: Breakdown of Garden Scenario Dose by Radionuclide. Shaded regions indicate where performance objectives would not be met.

is drawn into the well. The maximum dose of 25.5 mrem/yr occurs at 48,400 years. This peak is essentially equal to the 25 mrem/yr performance objective adopted through 10,000 years. During the 10,000-year period for which performance objectives are formulated, the only significant doses come from technetium-99 and iodine-129. Neptunium-237 and, to a much lesser extent, tin-126 become important after 100,000 years. This time delay is due to the delay in arrival resulting from sorption of these species as well as the depletion of the inventory of technetium-99 and iodine-129. At the time of the maximum dose, 68% of the dose is attributed to technetium-99 with the remainder from iodine-129. The technetium-99 exposure occurs approximately half through drinking water and half through ingestion pathways. The iodine-129 exposure occurs nearly entirely through the drinking-water pathway. Other exposure pathways and radionuclides are much less important. The doses for the garden scenario for the other compliance cases are shown in Figure 4.11. As in the farm scenario, the curves are all very similar, with minor variations arising from the assumptions about system properties. The discussion provided above for the dose curves for the compliance cases farm scenario also applies to the curves for the compliance cases garden scenario.

4.1.2.2 Groundwater Protection

This performance assessment has adopted a regulatory performance objective of 4 mrem/yr through the drinking-water pathway for 1,000 years after disposal (see Section 1.5.2). In addition, the 4-mrem/yr

Figure 4.11. Garden Scenario: Doses for Compliance Cases. Shaded regions indicate where performance objectives would not be met.

drinking-water dose has been adopted as a programmatic performance objective for a period of 10,000 years. Although this performance assessment is concerned with radiological releases, information is provided on the concentration of inorganic chemicals, with primary and secondary drinking-water standards provided as a point of reference.

The drinking-water scenario provides a basis for comparison in which the dose from drinking water is calculated assuming that the contaminant is mixed into the groundwater to the 4.6-m depth of the well screen. In addition, the concentration of chemicals identified in the primary and secondary drinking-water regulations is compared to drinking-water standards at 1,000 and 10,000 years. Figure 4.12 shows, for the central compliance case (Case 1.0), the dose from the drinking-water pathway along with a breakdown of radionuclides. Iodine-129 is the most important radionuclide, followed by technetium-99. The doses at 1,000 years are essentially zero (calculated $<1 \times 10^{-15}$ mrem/yr). At 10,000 years the dose reaches 4.1 mrem/yr, which is not significantly different from the 4-mrem/yr performance objective. After 10,000 years, the dose reaches a maximum peak of 18.7 mrem/yr at 48,400 years. After 100,000 years, the dose increases and then slowly declines to form a secondary peak of 8.6 mrem/yr at 173,000 years. The secondary peak is due almost entirely to neptunium-237.

Drinking water is a key exposure pathway for iodine. The iodine dose in the drinking-water scenario is higher than the total iodine dose in either the farm or garden scenario. The increased

Figure 4.12. Case 1.0, Central Compliance Case: Drinking-Water Dose to Maximum Individual. Shaded regions indicate where performance objectives would not be met.

concentrations obtained in the low-volume well more than compensate for the lack of additional pathways. Also, the amount of drinking water consumed in the drinking-water scenario is 2 L/d compared to 1.8 L/d in the farm and garden scenarios.

Figure 4.13 provides the drinking-water dose for the compliance cases. All cases meet the 4 mrem/yr regulatory performance objective at 1,000 years. As with the doses for the farm scenario, the doses are very low until after generalized cracking is assumed to occur at 5,000 years. The doses then rise rapidly. At 10,000 years, Case 1.0 is approximately at the programmatic performance objective and Cases 1.1 and 1.3 are within the programmatic performance objective. However, Case 1.2 exceeds 4 mrem/yr after approximately 9,000 years and reaches a dose of 6.9 mrem/yr at 10,000 years. All of the cases eventually exceed 4 mrem/yr. The treatment of the concrete roof of the vault may be why Case 1.2 produces a higher dose than Case 1.0. As discussed in Section 4.1.2.1, the concrete roof is assigned the water retention properties of backfill soil at 5,000 years, causing the pore water to drain from this region. All other cases in Figure 4.12 initially use the water retention properties for backfill soil in the concrete roof to avoid this drainage of pore water. Both Cases 1.0 and 1.2 experience similar drainage from the sides and bottom of the vault and catch basin concrete at 5,150 and 5,000 years, respectively. However, because the catch basin cavity is absent in Case 1.2, the amount of moisture draining is greater than in Case 1.0. Another possible reason for the dose in Case 1.2 to be higher than in other compliance cases is

Figure 4.13. Drinking-Water Doses for Compliance Cases. Shaded regions indicate where performance objectives would not be met.

the presence of low-conductivity cells in the top of the concrete in Cases 1.0, 1.1, and 1.3. These cells are not present in Case 1.2. The conductivity of these cells was reduced to prevent drainage of the pore fluid from the asphalt barrier into the concrete prior to degradation of the asphalt barrier.

In addition to the radiological impacts, the concentrations of inorganic chemicals listed in the primary and secondary drinking-water regulations were estimated. Chemical concentrations are provided for information purposes and are not associated with a performance objective. The concentrations are provided in Table 4.3 at 1,000 and 10,000 years and are based on mixing to a 4.6-m depth in the aquifer. As seen in the table, the concentrations at 1,000 years are extremely small and at 10,000 years only antimony (Sb) exceeds drinking-water standards. This result for antimony may be an artifact of the inventory estimate. The inventory of antimony is based on the analytical detection limit of a chemical analysis rather than a measured result. The amount of antimony may be much less than the detection limit. The transport properties for antimony in the grout and soil at the grout site are not well understood and it is possible that antimony will be fairly mobile. Therefore, the transport of antimony was modeled as occurring in transport group 1A, the most mobile set of transport properties. The concentration of nitrite is very near the limit at 10,000 years. However, nitrite is slowly oxidized to nitrate in the presence of air (Merck Index 1983). Due to the aerobic conditions in the Hanford soil, nitrite is expected to be converted to nitrate over the time period required to reach the aquifer. When looked at over time periods exceeding 10,000 years, concentration of several species exceed the drinking-water standards, including aluminum, beryllium, chromium, fluorine, nitrate, nitrite, and antimony. The inventory value for beryllium is based

Table 4.3. Concentrations of Primary and Secondary Drinking-Water Chemicals in the Aquifer. Concentrations assume mixing to a depth of 4.6 m, the assumed screened length of a monitoring well. Values exceeding primary or secondary drinking-water standards are shown in bold.

Species	Maximum for <1,000 yr (mg/L)	Maximum for <10,000 yr (mg/L)	Maximum for All Time (mg/L)	Drinking-Water Standard (mg/L)
Ag	0	0	4.9×10^{-5}	$1 \times 10^{-1(a)}$
Al	0	0	$8.4 \times 10^{-2(f)}$	5×10^{-2} to $2 \times 10^{-1(b)}$
As	0	3.8×10^{-7}	4.5×10^{-6}	$5 \times 10^{-2(c)}$
Ba	0	0	7.9×10^{-5}	1 ^(c)
Be	0	2.0×10^{-3}	$6.0 \times 10^{-3(g)}$	$4 \times 10^{-3(d)}$
Cd	0	0	8.8×10^{-5}	$5 \times 10^{-3(d)}$
Cl	0	8.4×10^{-2}	7.2×10^{-1}	$2.5 \times 10^{2(b)}$
CN(free)	0	1.3×10^{-3}	3.9×10^{-3}	$2 \times 10^{-1(d)}$
Cr	0	1.7×10^{-2}	$1.5 \times 10^{-1(h)}$	$5 \times 10^{-2(c)}$
Cu	0	0	1.2×10^{-4}	$5 \times 10^{-2(b)}$
F	0	3.8×10^{-1}	3.2 ^(h)	2 ^(e)
Fe	0	1.4×10^{-5}	1.7×10^{-4}	$3 \times 10^{-1(b)}$
Hg	0	0	7.7×10^{-6}	$2 \times 10^{-3(c)}$
Mn	0	5.1×10^{-6}	6.0×10^{-5}	$5 \times 10^{-2(b)}$
Ni	0	0	5.2×10^{-4}	$1 \times 10^{-1(d)}$
NO ₃ ⁻ (as N)	0	4.7	1.4×10^1	$1 \times 10^1(d)$
NO ₂ ⁻ (as N)	0	8.7×10^{-1}	2.6 ⁽ⁱ⁾	1 ^(d)
TOTAL N	0	5.6	1.7×10^1	$1 \times 10^1(d)$
Pb	0	0	4.7×10^{-4}	$5 \times 10^{-2(c)}$
Sb	0	1.0×10^{-2}	$3.1 \times 10^{-2(g)}$	$6 \times 10^{-3(d)}$
Se	0	0	2.2×10^{-4}	$1 \times 10^{-2(c)}$
SO ₄	0	8.5×10^{-1}	2.6	$2.5 \times 10^2(b)$
Zn	0	0	4.7×10^{-4}	5 ^(b)

- (a) From 40 CFR 143 National Secondary Drinking-Water Regulations. Limit in 40 CFR 141.11 eliminated at 56 FR 32113, 7/15/91.
- (b) From 40 CFR 143, National Secondary Drinking-Water Regulations.
- (c) From 40 CFR 141.11, National Primary Drinking-Water Regulations.
- (d) From 40 CFR 141.62, National Revised Primary Drinking-Water Regulations.
- (e) Secondary limit from 40 CFR 141. Primary limit is 4 mg/L.
- (f) Calculation of aluminum transport in soil used distribution coefficient of 30 ml/g, which is believed to be very conservative.
- (g) Inventory value is based on detection limit of analysis, not on measured result.
- (h) Chromium and fluorine are expected to have distribution coefficients greater than 125 ml/g. However, to reduce modeling they have been simulated with a grout distribution coefficient of 2 ml/g.
- (i) Nitrite is expected to convert to nitrate before reaching the aquifer.

on the detection limit of a chemical analysis, not on a measured result. The actual inventory of beryllium may be much less. The calculated releases of chromium and fluorine are very conservative. They were placed in transport group 3A (grout distribution coefficient of 125 ml/g) but were calculated in group 2A (grout distribution coefficient of 2 ml/g) to reduce the total number of transport simulations needed. An additional simulation with a grout distribution coefficient of 125 ml/g would likely show these species do not exceed drinking-water limits at any time. The transport of aluminum was calculated in group 3C, which uses a distribution coefficient in the soil of 3.0 ml/g. This value is believed to be very conservative. If a larger value were used, the resulting concentration would be expected to be below the secondary drinking-water standard. However, because this calculation would require an additional simulation specifically for aluminum, it was not performed. However, if the degradation described in the conceptual model actually occurs, the concentrations of nitrate would be expected to eventually exceed the drinking-water limit.

4.1.2.3 As Low As Reasonably Achievable (ALARA) Requirement

A performance objective to maintain the population dose below 500 person-rem/yr has been adopted (see Section 1.5.2). Two scenarios were used to evaluate the performance of the Grout Disposal Facility relative to the ALARA criteria: exposure through the Columbia River and exposure through a community well.

River Scenario. In the river scenario, the contamination from the Grout Disposal Facility is transported through the aquifer into the Columbia River. The contamination is then mixed into the river and exposure occurs through use of the river water by downstream populations (see Section 3.2.4.4). The river scenario is important because it is a scenario that will almost certainly occur. The exposure does not rely on any low probability event. It is expected that the Columbia River will be used by downstream populations for the foreseeable future.

Exposure in the river scenario results in extremely small individual doses because of the extent of dilution that occurs when the groundwater mixes with the Columbia River. Because of this, the population dose is very small despite the large population (5 million) exposed. The annual population dose is shown in Figure 4.14 for the four compliance cases. The dose remains below 0.1 person-rem/yr for all time in all cases, which is a factor of 5,000 less than the 500 person-rem/yr performance objective. Therefore, doses through the Columbia River easily meet the performance objectives for all time.

Community Well. The community well scenario was formulated to obtain a conservative measure of the potential population dose from the contamination in the aquifer following grout disposal (see Section 3.2.4.1). This scenario uses the entire contaminated groundwater plume to supply 80 people with water for the garden scenario. No dilution except the mixing to the well screen depth of 4.6 m is assumed.

Figure 4.14. Population Dose Versus Time for River Scenario for Compliance Cases

The total population dose is shown as a function of time for the compliance cases in Figure 4.15. The dose is significantly higher than the dose calculated for the river scenario. However, the doses are still two orders of magnitude less than the performance objective of 500 person-rem/yr.

4.1.3 Dose Analysis for Intruder Scenario

Section 3.2.4.5 of Chapter 3 describes the intrusion scenarios considered in this performance assessment. Tables 4.4 and 4.5 provide dose results for acute and chronic exposures for scenarios involving inadvertent intrusion. Table 4.4 provides the acute dose received by a driller who drills directly through the grout. Table 4.5 provides the chronic dose to an individual inhabiting the site following drilling. The tables provide the total dose as well as a breakdown of the most important radionuclides and the primary exposure pathway for that radionuclide. The results are calculated at 100, 300, 500, and 1,000 years after disposal. For the intruder scenarios, the impact decreases significantly with time because of decay of radionuclides (particularly cesium-137 and strontium-90) in the waste. Because the concentrations of radionuclides in the grouted waste will cause doses to intruders in excess of the performance objectives after the 100-year institutional control period, passive controls are incorporated in the design of the Grout Disposal Facility to warn and deter potential inadvertent intruders. These passive controls include a minimum 5-m depth to the top of the grout, a riprap cover layer, warning markers, and monuments, all of which are designed to be effective for at least 500 years. Five hundred years after disposal, the dose received is within the performance objective for both the acute and chronic exposures, and passive controls to warn and deter intruders are no longer required.

Figure 4.15. Population Dose for Community Well Scenario Versus Time for Compliance Cases

Table 4.4. Impacts for Drilling Intrusion Scenario^(a)

Intrusion Time (yr)	Total Dose ^(b) (mrem)	Key Radio-nuclides	Dose (%)	Primary Pathway
100	2,900	¹³⁷ Cs	100	External
300	37	¹³⁷ Cs	78	External
		¹²⁶ Sn	20	External
		²⁴¹ Am	2	Ingestion
500	8.4	¹²⁶ Sn	87	External
		²⁴¹ Am	7	Ingestion
		¹³⁷ Cs	4	External
1,000	7.8	¹²⁶ Sn	94	External
		²⁴¹ Am	3	Ingestion
		²³⁹ Pu	2	Ingestion

(a) Supplementary tables showing the results of the full inventory analysis are included in Appendix P, Section P.7.

(b) Effective Dose Equivalent (EDE). The performance objective is 500 mrem after 500 years.

Table 4.5. Impacts for Post-Drilling Residential Scenario

Intrusion Time (yr)	Total Dose ^(a) (mrem/yr)	Key Radio-nuclides	Dose (%)	Primary Pathway
100	24,000	¹³⁷ Cs	97	External
		⁹⁰ Sr	3	Ingestion
300	310	¹³⁷ Cs	77	External
		¹²⁶ Sn	19	External
		²⁴¹ Am	3	Inhalation
500	72	¹²⁶ Sn	82	External
		²⁴¹ Am	9	Inhalation
		¹³⁷ Cs	3	External
1,000	66	¹²⁶ Sn	89	External
		²⁴¹ Am	4	Inhalation
		⁹⁹ Tc	2	Ingestion

(a) Effective Dose Equivalent (EDE). The performance objective is 100 mrem/yr after 500 years.

4.1.4 Results for Other Release Scenarios

This section examines impacts from other release scenarios including radon release, upward diffusion without recharge, catastrophic flooding, and higher recharge.

4.1.4.1 Radon Release

A performance objective of $20 \text{ pCi/m}^2 \cdot \text{s}$ has been adopted for radon release to the surface (see Section 1.5.2). Radon is produced within the grout as part of the uranium-238 decay chain (see Table 3.45).

The small initial inventory of radium-226 causes the initial radon generation rate to be very small. When initially disposed, the rate of radon generation within the grout distributed across the disposal facility area (area of $8.944 \times 10^4 \text{ m}^2$) is estimated to be only $0.009 \text{ pCi/m}^2 \cdot \text{s}$, which is much less than the performance objective of $20 \text{ pCi/m}^2 \cdot \text{s}$ for release to the surface.

However, the inventory of species higher in the decay chain (especially uranium-234) is expected to cause ingrowth of radium-226 such that the radon generation increases over time. The predicted total activities over time are shown in Figure 4.16. Based on the total activity, the rate of radon generation in Figure 4.17 was calculated. As can be seen in Figure 4.17, the rate of radon generation within the grout

Figure 4.16. Predicted Activity in Grout of Radionuclides in the Uranium-238 Decay Chain

Figure 4.17. Predicted Rate of Radon-222 Generation in Grout

exceeds the performance objective for release to the surface of $20 \text{ pCi/m}^2 \cdot \text{s}$ after 4,000 years. Therefore, the mobility of the radon between the generation point in the grout and the ground surface must be examined.

The Grout Disposal Facility will provide a barrier to the escape of radon. The radon is generated within the grout and must escape the grout and engineered system and then diffuse up through the overlying cover material to be released at the surface. Because of the relatively short half-life of radon-222, the amount of radon actually reaching the surface is expected to be much less than the amount generated within the grout.

To estimate the radon flux to the surface, the radon was assumed to diffuse out of all sides of the grout block to a zero concentration boundary at the grout surface. The radon source out of the grout was then placed at the top of the grout and allowed to diffuse upward through 5 m of dry backfill soil. Parameters were selected to be very conservative. Details of the analysis are provided in Section 3.6.4.1. The diffusion profile penetrates about 100 cm into the grout block. Radon generated deeper in the grout block will decay without escaping from the grout. Only 12.3% of the radon escaping the grout reaches the top of the 5-m cover layer.

Based on the treatment described above, the peak radon-222 release from the Grout Disposal Facility would be about $8 \text{ pCi/m}^2 \cdot \text{s}$. This amount is less than the performance objective of $20 \text{ pCi/m}^2 \cdot \text{s}$. Because of the conservative nature of the treatment in the calculation, further refinement of the model would undoubtedly reduce the estimate. However, the calculated flux is less than the performance objective and further refinement is not necessary.

4.1.4.2 Upward Diffusion

This case examines the potential impacts if the recharge through the Hanford barrier is zero. With zero recharge, contaminants may diffuse upward through the soil and contaminate the surface. All properties in this case were the same as those for the central sensitivity case described in Section 3.6.1, except the recharge was set to zero. The dose is evaluated using the garden scenario without the drinking-water pathway. Additional detail is provided in Section 3.6.4.2.

The soil concentrations projected by transport group as a function of time are shown in Figure 4.18. This figure shows the concentration in the water present in the soil relative to the concentration in the grout pore solution. The soil moisture content is 4.6 vol%. The concentrations for transport groups 2A, 3C, and 4A exceed the concentration of group 1A because of the sorption in the grout. The maximum possible value for each of these curves is a value of 1.0 since the diffusion of species from the grout to the upper soil layer is driven by a concentration gradient in the water phase. Therefore, although the contribution to dose from groups 3C and 4A have not yet peaked, the technetium-99 peak is known to be of greater magnitude in terms of dose than the eventual secondary peak dominated by neptunium-237. The doses evaluated from the garden scenario are shown in Figure 4.19. As can be seen, the dose increases steadily up through 162,000 years, where it peaks at about 8 mrem/yr. Technetium-99 and tin-126

Figure 4.18. Relative Soil Concentrations Versus Time for Transport Groups with Zero Recharge

Figure 4.19. Doses for Garden Scenario Resulting from Upward Diffusion with Zero Recharge

account for 96% of the total peak dose with iodine-129 and neptunium-237 combining to account for 3.3%. The exposure is dominated by ingestion with external and dust inhalation pathways being orders of magnitude less. The relative impact of iodine-129 is less than in the groundwater-related garden scenario because there is not a drinking-water pathway in the upward diffusion garden scenario.

The dose rate of 8 mrem/yr is well below the 25 mrem/yr all-pathways performance objective. Therefore, low recharge does not present a concern in terms of upward diffusion to the soil above the grout vaults.

4.1.4.3 Catastrophic Flood

This case examines the impact of a catastrophic flood, 50,000 years after disposal, that physically disturbs and redistributes the grout over the upper 10 m of the Hanford Site. The dose is calculated using the farm scenario without the drinking-water pathway. Additional details are provided in Section 3.6.4.3.

The dose received in this scenario is 0.41 mrem/yr, which is much less than the 25 mrem/yr maximum individual performance objective established for the first 10,000 years. The dose is primarily due to external exposure from tin-126 and its daughter products (53%), and ingestion of technetium-99 (44%).

Other assumptions are possible concerning the area and depth over which the waste is dispersed. If the waste is dispersed over the 200 Area plateau (78 km²) to a depth of 4 m, the dose is 19 mrem/yr. This assumption was made previously in the Hanford Defense Waste Environmental Impact Statement (HDWEIS; U.S. DOE 1987). Alternatively, if the waste is dispersed over the Pasco Basin (4,850 km²) to a depth of 10 m, the dose is only 0.12 mrem/yr. In any case, the doses are below the performance objective of 25 mrem/yr.

4.1.4.4 Analysis of High Recharge

High recharge at the Hanford Site is not expected. Even without the presence of the Hanford barrier, the average recharge is expected to be only 0.1 cm/yr. However, it is possible that over the time frames being analyzed, significant changes in climate could occur. To evaluate the effect on the results of higher recharge, a case using a recharge rate of 5 cm/yr was simulated (see Section 3.6.4.4). Because this case does not represent an expected condition, the results are not compared to performance objectives. The 5-cm/yr recharge is applied from the beginning of the simulation. However, it is expected that the time required for such a climate change to occur would be thousands or tens of thousands of years. Thus, applying the recharge initially is conservative from a time-of-arrival standpoint.

The dose as a function of time for Case 1.4 is shown in Figure 4.20. Prior to 5,000 years, the dose is less than 0.1 mrem/yr. At 5,000 and 5,150 years, several changes occur in the model to simulate the staged degradation of the engineered system. The hydraulic conductivities of the asphalt barrier, concrete, and grout increase substantially and the moisture retention properties of the concrete are changed to those of backfill soil. The dose rises very quickly to a peak of 16 mrem/yr at 5,670 years. The high

Figure 4.20. Estimated Dose in the Farm Scenario Versus Time for a Staged Degradation of the Engineered System (Case 1.4) with Recharge Rate of 5 cm/yr. Simulation experienced a mass balance error higher than normally experienced (see Appendix P).

recharge greatly reduces the travel time through the vadose zone so that increases in the dose are more closely associated with the time of the changes in the engineered system. As staged degradation continues, the dose declines slightly and then reaches its maximum peak of 21 mrem/yr at 48,400 years. This peak is caused by the final increases in the hydraulic conductivity of the asphalt barrier and concrete vault, which occur at 40,000 years.

In simulating the increased recharge, a mass balance problem was detected that, to date, has not been identified and corrected. However, it is known that the mass balance problem occurs in the vadose zone. Appendix P provides discussion of the mass balance errors along with additional plots of intermediate results.

4.2 Sensitivity and Uncertainty Analysis

This section presents information concerning the uncertainties and sensitivities in the results. Sensitivities to parameters used in the analyses of the engineered system and vadose zone and in the groundwater analyses are examined. Sensitivities to dosimetry and inventory uncertainties are also addressed.

4.2.1 Engineered System and Vadose Zone

This section addresses sensitivities and uncertainties in the modeling of flow and transport through the engineered disposal system and the vadose zone. The sensitivity of the results is examined using a central sensitivity case, several design cases, and numerous sensitivity cases. The central sensitivity case is used as a common point of comparison against which other cases are compared. The central sensitivity case is much simpler than the compliance case simulations, which are used for comparison to performance objectives. The central sensitivity case includes cracks that are initially present in the asphalt barrier and concrete and includes biodegradation of the asphalt barrier over time. However, the extent of property changes over time is simplified compared to the compliance cases.

4.2.1.1 Central Sensitivity Case Simulation

The central sensitivity case (Case 2.0) is used in this performance assessment as a central point for comparison of design and sensitivity cases. Sections 3.6.1 and 3.6.5.1 provide a complete description of the central sensitivity case.

A plot of the fractional release by transport group for the four most important transport groups for groundwater-related scenarios is shown in Figure 4.21. These transport groups (with the key radionuclide for each) are group 1A, iodine-129; group 2A, technetium-99; group 3C, neptunium-237; and group 4A, uranium-238. This figure is not species specific and therefore does not include the inventory of the individual species or the effects of radioactive decay. It illustrates the fraction of the inventory released to the aquifer in a given year for the set of transport properties associated with the group. This information is then combined with the site recharge; the mixing at the well intercept; exposure scenario assumptions; and the inventory, half-life, and dose factors for each radionuclide to calculate the dose for each exposure scenario (see Section 3.5.1). The central sensitivity case and the associated design and sensitivity cases are not considered for comparison to performance objectives because they do not incorporate a complete representation of gradual or staged degradation and the influence of degradation on flow and transport. However, to provide a common point of comparison, the dose for the farm scenario has been calculated for each case. A plot of the estimated dose for the farm scenario for the central sensitivity case is provided in Figure 4.22.

The dose is negligible until after 2,000 years. The 2,000-year delay in arrival is primarily due to the time required for advection through the vadose zone to the aquifer. To simplify modeling, the cracks are modeled as being present at the beginning of the simulation. Therefore, the 2,000-year delay does not include any period of intact performance of the engineered system. A delay for the travel time through the saturated zone to the well is included but is negligible relative to the travel time in the vadose zone.

The farm scenario dose rises between 2,000 and 10,000 years and reaches a plateau of 3.0 mrem/yr at 20,000 years, primarily from the iodine-129 and technetium-99. The plateau is maintained until 90,000 years, at which time the asphalt barrier is assumed to complete degradation and is assigned the

Figure 4.21. Fractional Release by Group Versus Time for Central Sensitivity Case (Case 2.0). Most important radionuclides in transport groups: iodine-129, group 1A; technetium-99, group 2A; neptunium-237, group 3C; and uranium-238, group 4A.

properties of backfill soil. Between 90,000 and 100,000 years, the dose rises to a new maximum of 17.3 mrem/yr. The dose from technetium-99 and iodine-129 drops off over the next 100,000 to 200,000 years due to depletion of the inventory of these species. Meanwhile, the dose from neptunium-237 is increasing and supporting a declining plateau of about 4 mrem/yr. The substantial delay in the neptunium-237 peak is due to the sorption in the soil. The release of species in transport group 4A is controlled by the strong sorption in the grout. When the barrier degrades at 90,000 years, the release quickly reaches a stable plateau. However, group 4A contributes less than 0.2% of the total dose at the peak (primarily from uranium isotopes). Modeling was halted at 660,000 years.

To confirm that the radionuclides in transport groups 2B, 3A, and 4D do not contribute significantly to dose, these groups were simulated for the central sensitivity case and compared to the results presented above. The fractional release curves are shown in Figure 4.23. The maximum dose contribution from species in these transport groups was approximately 0.02 mrem/yr. Group 4D was still increasing at 600,000 years, so modeling was continued up to 1 million years. The dose has peaked at this point at a plateau of about 0.001 mrem/yr. Because of the sorption in the grout and soil, grout is an excellent

Figure 4.22. Farm Scenario Dose Versus Time for Central Sensitivity Case

waste form for transport group 4D radionuclides (plutonium, thorium-230, and americium-241). Because of the minor impacts of the species in transport groups 2B, 3A, and 4D, nearly all of the sensitivity cases have been analyzed using only transport groups 1A, 2B, 3C, and 4A to reduce the amount of computation required.

The moisture contents in the vadose zone for the central sensitivity case at 10,000 years are shown in Figure 4.24A. The moisture contents are similar between the central sensitivity case (Case 2.0) and Case 1.0, as can be seen by comparing Figures 4.24A and 4.1. The moisture contents in the concrete are higher in Figure 4.24A because the water retention properties of the concrete are changed to those of backfill soil at 5,150 years in Case 1.0 to simulate degradation. By 10,000 years, the moisture has drained from the concrete into the underlying sediments. In addition, the moisture contents beneath the vault are slightly lower in Figure 4.24A because of the degraded properties of the grout, concrete, and asphalt barrier in Case 1.0.

Figure 4.24B provides an expanded view of the top portion of the vault at 1,000 years. At this time, the moisture contents are nearly steady and the degradation of the asphalt barrier is not yet significant. The contours on top of the vault do not appear to be disrupted, a condition that would be visible if perched water were forming. Therefore, it is concluded that there is not a tendency for water to perch on top of the vault as might happen with disposal in a wetter climate.

Figure 4.23. Fractional Release Curves for Less Important Transport Groups

Figure 4.25 provides the relative concentration contours for iodine-129 at 10,000 years. The model does not include any sorption of iodine-129 in the engineered system, vadose zone, or saturated zone. Figure 4.25 indicates an advective-dominated transport in the vadose zone. The concentration profiles do not penetrate to any degree above the vault. Inside the vault it appears that the contaminant has reached a fairly uniform concentration with the majority of the concentration gradient occurring across the asphalt barrier. Depletion of the grout inventory is primarily at the top corners where cracks have been assumed to occur. Advective flow in the grout causes release in the lower cracks, resulting in less depletion of the grout concentration near these cracks. Some distortion of the contours can be seen between the backfill and the Hanford formation sandy sequence (aligned with the bottom of the vault), but there is little change in the contours between the Hanford sandy sequence and the lower gravel sequence.

The release of contaminants in the central sensitivity case is much more controlled by the release from the cracks, while much of the release in the compliance cases occurs directly through the bottom of the engineered system because of the assumed degradation. This difference in release location can be seen by comparing the concentration contours beneath the vault in Figures 4.25 and 4.4.

Figure 4.24A. Moisture Content Contours for the Central Sensitivity Case (Case 2.0) at 10,000 Years (numbers to right indicate contour lines shown)

Figure 4.24B. Moisture Content Contours for the Central Sensitivity Case (Case 2.0) Showing Top Portion of Vault at 1,000 Years (numbers to right indicate contour lines shown)

Figure 4.25. Relative Concentration Contours for Iodine-129 in the Central Sensitivity Case at 10,000 Years (numbers to right indicate contour lines shown)

4.2.1.2 Design Cases for Engineered System

Design cases were simulated to determine the relative importance of various features of the disposal system. The calculations were performed using the PORFLOW code and the same grid and material properties as in the central sensitivity case (see Section 3.5.2 for a description of PORFLOW). Problems similar to the design cases have been analyzed previously using highly simplified models. However, these problems are analyzed again here using a level of sophistication equivalent to the central sensitivity case to provide a comparison. The design cases consist of a series of simulations, each with features of the disposal system either present or not present in the model. When compared to the central sensitivity case, these cases provide insight into the value of the barriers and an understanding of which features are important in the system.

The design cases indicate that, despite the assumption of cracking at the top and bottom corners, the concrete vault and asphalt barrier both play important roles in reducing the initial release of mobile species from the grout. In addition, the gravel layer over the top of the cracked asphalt barrier and concrete vault greatly reduces the initial release by reducing flow through the cracks. The presence of the RCRA cover has no beneficial effect on the performance of the system. Additional detail on the design cases is provided in the remainder of this section.

The design cases are described in Section 3.6.5.2. The calculated farm scenario doses for the design cases are plotted in Figure 4.26 to provide a comparison among cases. However, because these cases do not represent expected conditions, a comparison to performance objectives is not appropriate. For example, the dose estimated for grout placed directly in the backfill soil is important from the standpoint of understanding the contribution of barriers around the grout, but does not represent an expected condition for the vaults. The simulation including only grout (Case 2.1A) reaches a peak of 64 mrem/yr after 8,500 years. When the concrete vault, gravel layer, and RCRA cover are added to the model (Case 2.1B), the dose at the peak is reduced to 32.4 mrem/yr and the peak is delayed until 11,800 years. If the gravel is removed from the problem and the asphalt barrier is added (Case 2.1C), the dose is reduced to 22.8 mrem/yr and the time of the peak dose is not changed. As noted in Section 3.6.5.2, the initial conditions in Case 2.1C were slightly different than they were in the other design cases. The initial moisture content in the backfill soil in Case 2.1C was 10 vol% and the initial pressure head in the grout was -75 cm, rather than 5.6 vol% moisture and -338 cm as in the other design cases. Because of the initial conditions, there is some increase in the initial release and transport. This increase may contribute to the slightly earlier arrival time for Case 2.1C as seen in Figure 4.26. The peak dose does not occur until 11,800 years, so the timing and magnitude of the peak should be less affected by the initial conditions than is the arrival time. Because the design cases do not consider water vapor diffusion, the beneficial effect of the asphalt barrier in reducing water vapor diffusion is not included in Figure 4.26. Also, note that the beneficial effect of an intact asphalt barrier is greatly reduced by the assumption of cracking of the barrier in line with cracks in the concrete. The asphalt barrier has some beneficial effect by reducing ionic diffusion and advection through the intact concrete but has little effect on the cracks because it is assumed to be cracked at the same locations as the concrete. When both the gravel layer and the asphalt barrier are present, the release is decreased substantially compared to only one of the two components

Figure 4.26. Farm Scenario Doses for Design Cases. The cases shown include the following: Case 2.1A, grout placed in backfill soil; Case 2.1B, grout placed in a concrete vault without the asphalt barrier but with a gravel layer and RCRA cover; Case 2.1C, grout in a vault with an asphalt barrier and RCRA cover but no gravel layer; Case 2.1D, grout in a vault with an asphalt barrier and gravel layer but without a RCRA cover; Case 2.0, grout in a vault with an asphalt barrier, gravel layer, and RCRA cover. Case 2.1D and Case 2.0 coincide on plot.

alone. This can be seen by comparing Case 2.1D (both gravel and asphalt barrier) to Case 2.1B (gravel layer) and Case 2.1C (asphalt barrier). The presence of the gravel over the cracks in the top of the diffusion barrier reduces the amount of advection occurring through these cracks. The dose is reduced to 3.1 mrem/yr and the peak is delayed to 22,000 years. Finally, the RCRA cover is unimportant at 0.1-cm/yr recharge and reduces the dose by less than 2% (compare Case 2.0 and Case 2.1D).

4.2.1.3 Sensitivity Cases for Engineered System

The sensitivity cases described in Section 3.6.5.3 were simulated to determine the importance of the material properties assigned in the central sensitivity case simulation. The sensitivity cases are derived from the central sensitivity case. However, the qualitative conclusions about the importance of various parameters also apply qualitatively to the compliance cases. The results of the sensitivity cases provide the conclusions listed below.

Sensitivity Case Conclusions. Grout - The sorption of technetium-99 in the grout provides more than a factor of two reduction in the peak dose prior to asphalt barrier degradation because of the separation of the arrival of iodine-129 and technetium-99. The system is only moderately sensitive to increases in the saturated hydraulic conductivity of the grout. The release is sensitive to reductions in grout saturated hydraulic conductivity only after the asphalt barrier is assumed to degrade. The results are not sensitive to reductions in the grout diffusivity or initial condition in the grout.

Asphalt - The simulation is moderately sensitive to allowing advection within the asphalt barrier region. Doubling the biodegradation rate results in barrier degradation and the associated peak dose occurring 45,000 years earlier, but the peak dose is only slightly higher. Assumptions about porosity in the asphalt barrier as the barrier degrades have little impact on the results.

Cracking - The simulation results are very sensitive to the assumptions about cracking used for the grout and concrete. Elimination of all cracking, or elimination of either the top cracks or the bottom cracks, substantially reduces the release from the system prior to asphalt barrier degradation. Using the hydraulic properties of gravel in the cracks rather than those of backfill soil also significantly reduces the impact of cracking. Changes in the size and location of cracks also impact the results.

RCRA Cover - The RCRA cover has little or no effect on the transport of contaminants from the engineered system to the aquifer for a 0.1-cm/yr recharge. Even at 5-cm/yr recharge the effect is small, because the RCRA cover transmits water at a rate up to its saturated hydraulic conductivity (3.16 cm/yr).

Vapor Return - Inclusion of a water source to simulate vapor diffusion into cracks near the upper regions of the vault produces a moderate increase in the dose.

Vadose Zone - The primary sensitivities of the simulation to the presence of the vadose zone are listed below:

1. The vadose zone provides a substantial delay of the initial arrival of contaminants at the aquifer.
2. The impacts from sudden changes introduced in the engineered system to simulate degradation are smoothed prior to contaminants reaching the aquifer. (In reality, these changes would probably be gradual anyway.)
3. The sorption of neptunium-237 in the soil produces a significant delay that prevents neptunium-237 from arriving at the aquifer at the same time as technetium-99 and iodine-129.

Additional Sensitivity Case Details. This section provides additional supporting details for the conclusions listed above.

Grout. The farm scenario doses for sensitivity cases involving grout parameters are plotted together in Figure 4.27. The central sensitivity case (Case 2.0) is included for comparison. Case 2.2A illustrates the sensitivity of the results to the sorption of technetium-99 in the grout. Eliminating the sorption of technetium-99 causes this radionuclide to arrive simultaneously with the iodine-129. The simultaneous arrival of technetium-99 and iodine-129 increases doses at the first peak from 3.0 to 8.1 mrem/yr. When the barrier degrades at 90,000 years, the peak is increased from 17 to 26 mrem/yr but then drops off more rapidly because of the simultaneous depletion of iodine-129 and technetium-99.

The effect of increasing the saturated hydraulic conductivity of the grout by a factor of 100 is shown by Case 2.2B. The dose on the first peak increases from 3.0 to 4.3 mrem/yr and the peak after asphalt barrier degradation increases from 17 to 21 mrem/yr. Decreasing the saturated hydraulic conductivity by a factor of 10 (Case 2.2C) results in only a small reduction of the first peak from 3.0 to 2.8 mrem/yr because other features in the system are restricting flow through the engineered system. However, the dose at the 100,000-year peak after the asphalt barrier degrades is reduced from 17 to 11 mrem/yr.

Figure 4.27. Sensitivity of Results to Assumptions Involving Grout. Cases included are Case 2.2A, no sorption of technetium-99 in the grout; Case 2.2B, factor of 100 increase in grout hydraulic conductivity; Case 2.2C, factor of 10 decrease in grout hydraulic conductivity; Case 2.3D, factor of 100 increase in grout diffusivity; Case 2.3E, initial condition for pressure in grout of -5,000 cm rather than -338 cm. Doses calculated using the farm scenario.

The dose result is not very sensitive to a two order-of-magnitude reduction in the diffusion coefficient for all radionuclides (Case 2.2D). A reduction in the diffusivity produces a small, counter-intuitive increase in doses both at the first peak (3.2 versus 3.0 mrem/yr) and second peak (19 versus 17 mrem/yr). The reason for the increase is that the release is controlled by advection and the higher diffusion coefficient allows more diffusion into the concrete regions where the hydraulic conductivities are lower. Appendix P provides additional detail.

Case 2.2E shows the effect of changing the initial pressure head of the grout from -338 cm to -5,000 cm. The impact of the initial condition of the grout is to delay the time of arrival of contaminants at the aquifer by about 2,000 years. The eventual peak impacts are not affected (first peak 2.96 versus 3.00 mrem/yr for the central sensitivity case).

Asphalt. Sensitivity cases involving the asphalt barrier are compared using the farm scenario dose in Figure 4.28. Sensitivity Case 2.3A examines the importance of flow within the asphalt barrier

Figure 4.28. Sensitivity of Results to Assumptions Involving Asphalt Barrier. Cases included are Case 2.3A, asphalt barrier given a saturated hydraulic conductivity of 1×10^{-11} and concrete water retention properties; Case 2.3B, asphalt biodegradation rate doubled; Cases 2.3C/2.3D, effect of porosity in degrading barrier (comparable only to each other); Case 2.0, central sensitivity case simulation. Doses calculated using the farm scenario.

by modeling the asphalt barrier with the water retention properties of concrete and a saturated hydraulic conductivity of 1×10^{-11} cm/s. The value for saturated hydraulic conductivity is conservatively high based on nitrogen permeability measurements without correction for viscosity or surface properties. By comparison, the central sensitivity case used a value of 1×10^{-20} cm/s, which was intentionally selected to prevent advection within the barrier region. As can be seen in the figure, the presence of flow within the asphalt barrier causes an increase in the release before the asphalt barrier degrades.

Case 2.3B examines the effect of doubling the biodegradation rate from 1 cm/1,000 yr to 2 cm/1,000 yr. The accelerated biodegradation causes the peak normally seen at about 100,000 years to arrive at 55,000 years and reach a slightly higher peak (23 versus 17 mrem/yr). The increase is due to the lower inventory depletion when the barrier degrades.

Case 2.3C and 2.3D examine the effect of the porosity assigned to the diffusion barrier. These cases model 1-mm cracks in the asphalt barrier on 1-m spacing and do not have major discrete cracks in the concrete or asphalt barrier. Because of these differences and others, Cases 2.3C and 2.3D should not be compared to the central sensitivity case. The two cases are identical except for the porosity assigned to the asphalt barrier. Case 2.3D uses a porosity of 0.202, corresponding to the maximum air void fraction of the barrier plus the volume fraction asphalt. Case 2.3C uses a porosity of 0.04, corresponding to the maximum air void content for the barrier. The results indicate that, for this case, the use of 0.04 is only slightly more conservative, but that this parameter makes little difference. The simulations were calculated for only 25,000 years to reduce the computational time required.

Cracking. A number of sensitivity cases were performed to determine the sensitivity to various assumptions about cracking. A plot of the doses for the farm scenario, calculated for the various cases, is provided in Figure 4.29. The central sensitivity case (Case 2.0) is plotted as well for comparison. All of the alternate cracking assumptions examined resulted in lower doses prior to complete biodegradation of the asphalt barrier than in the central sensitivity case.

Case 2.4A examined a different cracking configuration. The cracks in the top corners of the asphalt barrier are aligned with the top of the concrete vault rather than the top of the grout. The cracks in the asphalt barrier are 1-cm wide at the top and 0.5-cm wide at the base of the vault. The concrete roof of the vault contains roof plant joints (0.2 cm/m) and the sides of the vault contain four construction joint cracks (0.1- to 0.85-cm wide). Case 2.4B is similar to 2.4A, except the cracks in the asphalt barrier are larger. The cracks at the top corners of the asphalt barrier are 18.9- to 21.3-cm wide and the cracks at the base of the vault are 10-cm wide. In both cases the concrete roof was given the water retention properties of backfill soil to avoid numerical difficulties that would have greatly extended the simulation time. Based on Cases 2.4A and 2.4B, it is concluded that cracks in the barrier that are not aligned with cracks in the concrete (and hence do not expose the grout) have a significantly lower impact. The differences in

Figure 4.29. Farm Scenario Dose for Sensitivity Cases Involving Cracking Assumptions. Cases included are Case 2.4E, cracks in upper corners only; Case 2.4D, cracks at lower corners only; Case 2.4C, gravel properties used in cracks; Case 2.4B, alternate cracking configuration; Case 2.4A, alternate crack configuration with small cracks; Case 2.4F, no cracking in asphalt barrier or concrete.

the doses between Cases 2.4A and 2.4B are believed to be due to the differences in convergence criteria specified for solving the problem. The crack size is not thought to be a sensitive parameter.

Case 2.4E investigates the sensitivity to the crack in the asphalt barrier at the bottom corner of the vault. All parameters are the same as in the central sensitivity case except that the crack in the asphalt barrier at the base of the vault is eliminated. The dose does not increase above 0.001 mrem/yr for over 5,000 years. The added delay compared to the central sensitivity case occurs because the cracks near the upper corners expose the noncontaminated grout rather than contaminated grout. By eliminating the lower crack (which directly exposes contaminated grout), the arrival time is shifted by about 3,000 years. The dose then increases steadily but remains below 1 mrem/yr until the barrier completely degrades at 90,000 years. The peak dose, obtained when the asphalt barrier degrades, is 19 mrem/yr, which is slightly more than the 17 mrem/yr in the central sensitivity case. This difference is due to less depletion of the inventory. The final plateau from the neptunium-237 is virtually unaffected by the change in assumption.

Although the initial arrival in this case is sooner,^(a) the performance is very similar to the sensitivity case without cracking (Case 2.4F). This case indicates that the impact of cracking (neglecting water vapor return) is very minor if there is not an advection pathway both into and out of the grout.

Case 2.4D includes cracks at the lower corners of the system but eliminates the cracks at the upper corners. Compared to the central sensitivity case, the dose curve starts at about the same time but increases more slowly, not exceeding 0.1 mrem/yr until approximately 10,000 years. After the barrier degrades, the peak dose is higher than that for the central sensitivity case because the extent of inventory depletion is less prior to barrier degradation. Comparing Cases 2.4D and 2.4E indicates that the lower crack is a more important contributor to release than is an upper crack. This may be because the lower crack directly exposes contaminated grout while the upper cracks expose the cold grout cap.

Case 2.4C used the hydraulic properties of gravel to represent the cracks in the asphalt barrier rather than those of backfill soil. In the central sensitivity case, hydraulic properties for backfill soil were selected to prevent the hydraulic properties for cracks from limiting release. In reality, cracks probably will not fill with soil. Cracks in the top of the vault will be covered by the gravel layer, which will prevent infiltration. Horizontal cracks and cracks in the bottom barrier are not expected to fill with soil. As crack surfaces in the barrier degrade, an asphalt-deficient region filled with the barrier aggregate will be created. If any of the organic material remains, the aggregate may have little affinity for water. In this case the hydraulic properties of the crack may be more like those of a gravel than those of a backfill soil. The initial arrival time obtained using gravel properties is about the same as in the central sensitivity case. However, the dose levels off at approximately 0.6 mrem/yr until just before the asphalt barrier degrades at 90,000 years. After the asphalt barrier degrades, the impact is increased from 17 to 21 mrem/yr because of the lesser extent of inventory depletion. This case demonstrates that the hydraulic properties associated with cracks can significantly affect release while the remainder of the barrier is intact.

Case 2.4F is the same as the central sensitivity case except that cracking of the asphalt barrier and concrete is not included. Cracks were included in the central sensitivity case because of the difficulty in defending long-term integrity of the engineered system. Although it is possible that cracking of the asphalt barrier will be minor and that cracks may heal since the system is in compression at all times, this possibility is difficult to rigorously support for an indefinite period of time. This case provides insight into the role of cracks in the performance of the system. The dose remains below 0.01 mrem/yr until 25,000 years and below 0.1 mrem/yr until 55,000 years. The dose then increases as the barrier is thinned

(a) The earlier arrival observed in Case 2.4E is not apparent because of the scale of the graph. However, at 1.1×10^4 years, the dose in Case 2.4E is 1.1×10^{-2} mrem/yr, while Case 2.4F is only 3.9×10^{-4} mrem/yr.

by biodegradation and increases sharply after complete biodegradation of the barrier to a peak of 20 mrem/yr. This peak dose is greater than the 17 mrem/yr in the central sensitivity case because of the lower extent of inventory depletion.

Case 2.4F illustrates the extreme sensitivity of the system to the assumption of cracks in the asphalt barrier. If assumed to be functioning as designed, the asphalt barrier prevents advection, resulting in a diffusion-controlled release. In this case the barrier is extremely effective in limiting the release to very low levels for an extended period. The absence of cracks in the concrete had some effect but its effect was not nearly as dramatic as the effect of the barrier.

RCRA Cover and Recharge Rate. Figure 4.30 shows the farm scenario dose for sensitivity cases involving the RCRA cover and the rate of recharge. When the recharge rate is 0.1 cm/yr, the effect of the RCRA cover can be seen by comparing Case 2.5C, which does not contain the RCRA cover, to the central sensitivity case (Case 2.0). As can be seen, the RCRA cover has no impact on the results at a recharge rate of 0.1 cm/yr. At a recharge rate of 5 cm/yr, the effect of the RCRA cover can be seen by comparing Cases 2.5B, which has the RCRA cover, and Case 2.5A, which does not. With a recharge rate of 5 cm/yr, the RCRA cover has some beneficial, but minor, effect. The effect of the recharge rate can be

Figure 4.30. Farm Scenario Dose for Sensitivity Cases Involving the RCRA Cover. Cases included are Case 2.5B, 5-cm/yr recharge with RCRA cover; Case 2.5C, 0.1-cm/yr recharge without RCRA cover; Case 2.5A, 5-cm/yr recharge without RCRA cover; Case 2.0, central sensitivity case (0.1 cm/yr recharge with RCRA cover). Case 2.5C and Case 2.0 coincide in the plot.

seen by comparing Case 2.5B to Case 2.0. The higher recharge rate results in a much earlier arrival and a higher maximum dose prior to complete degradation of the asphalt barrier. One key element in this sensitivity is that the barrier and concrete are cracked at both the top and bottom corner as described in Section 3.6.5.1 for the central sensitivity case. In the compliance cases, the large crack at the bottom corner was not included. This crack allows a flow path through the system and increases the impact of high recharge.

Water Vapor Diffusion. Water vapor diffusion through an intact asphalt barrier can be shown to be unimportant relative to the performance objectives using very simple calculations (see Appendix L). However, cracks in the asphalt barrier may contribute to significant increases in the rate of water vapor diffusion through the barrier. To determine the significance of water vapor diffusion, the central sensitivity case was run with a water source of approximately 0.12 L/yr per meter of vault introduced into each of the six cracks in the barrier. The additional moisture was introduced uniformly within the nodes representing the crack through the concrete. The resulting doses are compared to the central sensitivity case in Figure 4.31. As can be seen in the figure, the addition of water vapor diffusion results in a small increase in dose. The simulation for Case 2.6A was halted at 90,000 years.

Figure 4.31. Comparison of Farm Scenario Doses Calculated for the Central Sensitivity Case with (Case 2.6A) and Without (Case 2.0) a Vapor Diffusion Water Source

This simulation experienced a mass balance error of approximately 10% (mass increase). This error is greater than that for cases which did not include water vapor return. Appendix P provides greater detail on the mass balance error.

Vadose Zone. Case 2.6B was designed to determine the effect of the vadose zone on the simulation results. During execution of the central sensitivity case, a line was defined horizontally across the problem domain, passing between the bottom of the asphalt barrier and the soil. The flux of contaminant crossing this line as a function of time was recorded. The contaminant was then immediately placed in the aquifer. This case eliminates the effects of the vadose zone on the transport of contaminants from the exterior of the engineered system to the aquifer. However, the vadose zone is still active in the problem and affects liquid fluxes and concentration gradients that have an influence on the release from the engineered system.

Figure 4.32 provides a comparison of the farm dose calculated for Case 2.6B to that calculated for the central sensitivity case. The most striking difference is that the initial dose occurs very early,

Figure 4.32. Comparison of Farm Scenario Doses for Case 2.6B (vadose zone eliminated) and Case 2.0 (central sensitivity case)

reaching 0.002 mrem/yr after only 7 years. The dose begins forming a plateau after only about 1,000 years, reaching a maximum of 3.6 mrem/yr at 10,000 years. This level is slightly greater than the maximum for the central sensitivity case plateau of 3.0 mrem/yr. The peak obtained when the barrier degrades is much sharper than in the central sensitivity case. The dose reaches a value of 274 mrem/yr and falls back to 23 mrem/yr over the next 15,000 years. This peak is considerably higher than the 17.3 mrem/yr in the central sensitivity case. The difference is due to the absence of any smoothing on the instantaneous change when the barrier degradation is completed. In addition, the neptunium-237 is contributing to the peak that is normally dominated by iodine-129 and technetium-99. From this peak the dose declines over time, reaching 6.8 mrem/yr at 540,000 years.

From this case it can be seen that the primary effect of the unsaturated zone is to delay the initial arrival of contaminants at the well. In addition, the vadose zone provides some smoothing of the sudden spike that occurs following the complete degradation of the asphalt barrier, and also separates the arrival of the neptunium-237 from the iodine-129 and technetium-99. The sharpness of this peak is somewhat artificial since the completion of asphalt barrier degradation would not be expected to occur simultaneously at all locations on one vault or between different vaults in a field.

4.2.2 Uncertainties in Groundwater Transport

The approach to uncertainties in groundwater transport calculations is discussed in Section 3.6.5.4. The groundwater model and the resulting well intercept factor have been examined for sensitivity to three factors: 1) recharge rate, 2) pumping rate, and 3) number of vaults. Values of the well intercept factor are shown in Table 4.6 for variations of these parameters. The first two parameters, recharge and

Table 4.6. Well Intercept Factors as a Function of Recharge, Pumping Rate, and Number of Vaults

Recharge (R) Q(Pump) (Q _w)	Number of Vaults		
	33	4	1
R = 0.1 cm/yr Q _w = 0	0.010	0.00253	0.00148
R = 0.1 cm/yr Q _w = 45 m ³ /d	0.00308	0.000731	0.0000867
R = 5 cm/yr Q _w = 0	0.415	0.256	0.0526
R = 5 cm/yr Q _w = 45 m ³ /d	0.105	0.0364	0.00433

pumping rates, affect groundwater flow. The recharge rate applied to the surface of the site affects flow at the scale of the site while the pumping rate affects the aquifer only in the immediate vicinity of the well. The third parameter, number of vaults, actually involves the inventory and surface area associated with 33, 4 and 1 vaults for disposal, and the orientation of the vaults to the groundwater flow.

Variations in the well intercept factor as a result of varying recharge and pumping rates are a function of the volume of contaminated water infiltrating through the Grout Disposal Facility, the direction and magnitude of groundwater flow, and the orientation of the Grout Disposal Facility boundary to the flow field. The background or natural recharge rate case, including a 0.1-cm/yr recharge at the Grout Disposal Facility, produced a west-to-east groundwater flow beneath the Grout Disposal Facility (see Section 3.4.4). The higher recharge rate case, based on a 5-cm/yr increment everywhere across the Hanford Site, produced a general northeasterly flow beneath the Grout Disposal Facility; the groundwater then flows to the east upon encountering Gable Mountain. Because the groundwater is in the vicinity of Gable Mountain and the flow field turning toward the east, the average groundwater hydraulic gradient and velocity are both lower in the high recharge case than in the low recharge case (see Section 3.4.4). Compared to the background or natural recharge cases, the higher recharge rate cases all exhibit less mixing with uncontaminated water in the well. This is a direct result of the greater amount of recharge through the Grout Disposal Facility becoming a substantial source of water making up the flux of groundwater in the upper portion of the unconfined aquifer that is drawn to the partially penetrating groundwater well. When compared to the low pumping rate well, the pumping of a well at 45 m³/d creates somewhat higher groundwater flux in the aquifer at the boundary of the site for each of the recharge cases. Two additional recharge rate cases were simulated to evaluate the potential influence of irrigated agriculture on the thickness of the unsaturated zone and the well intercept factor. The results of these cases are compared to the natural recharge and 5-cm/yr incremental recharge in Appendix P.

A different rectangular land area is associated with each of the three vault configurations examined, and the orientation (i.e., longitudinal axis orientation to north-south) of the land area varies from east-west in the 33- and 1-vault cases to north-south in the 4-vault case. Surface area is used to calculate the flux of water through the portion of the Grout Disposal Facility associated with the vaults. The land area associated with different cases is not linearly related to the number of vaults because of the layout of the vaults within the Grout Disposal Facility. Orientation plays a role in defining the cross-section of the aquifer associated with the Grout Disposal Facility, i.e., orthogonal to the direction of groundwater flow.

Taken together the variability in disposal site area and orientation, and in groundwater flow field, produces a nonlinear response in the well intercept factor. While the response is not linear, in all cases of recharge and pumping rate the trend is for increased mixing (smaller well intercept factor) with a decrease in the number of vaults. All analyses reported in the performance assessment are based on a 33-vault configuration. Most are based on background or natural recharge, denoted in Table 4.6 as $R = 0.1$ cm/y. These analyses use the well intercept factors of 0.010 and 0.00308 for low groundwater pumping (drinking water and irrigated garden) and high groundwater pumping (irrigated 2-hectare farm) scenarios. The higher recharge cases have used the 0.415 and 0.105 well intercept factors, respectively. Table 4.6

reveals that reducing the number of vaults does not produce proportional decreases in the well intercept factor. Reducing from 33 to 4 vaults produces about a factor of 4 reduction in the well intercept factor for the 0.1 cm/yr recharge case, and only a factor of 1.6 to 3 reduction for the 5-cm/yr recharge case. This difference is a result of the different orientations of the 33- and 4-vault layouts. Reducing the number of vaults from 33 to 1 produces only a factor of 7 change in the low pumping rate cases, but a factor of 20 to 30 improvement in the high pumping rate cases. The factor of 7 improvement is due to both the contaminated infiltration and the groundwater flux being reduced in the single vault scenario.

4.2.3 Groundwater Pathway Dosimetry

A sensitivity analysis was performed for dosimetry parameters in the irrigated farm, irrigated garden, and river scenarios to determine the influence of these parameters and their associated uncertainties on the dose estimates (see Section 3.6.5.5). In the irrigated farm scenario, the sensitivity analysis was conducted separately for each radionuclide that contributes significantly to the total individual dose, including iodine-129, technetium-99, neptunium-237, tin-126, cesium-135, and selenium-79. Detailed results of the dosimetry sensitivity analysis are presented in Appendix N. For all radionuclides except tin-126, the drinking-water consumption rate controlled the total dose uncertainty. Parameters related to animal product ingestion pathways (pasture irrigation rates and consumption of beef and milk) dominated the uncertainty for tin-126, and also contributed significantly to the total uncertainties in dose for the other radionuclides. These parameters accounted for 68% to 89% of the total uncertainty in the effective dose equivalent.

Uncertainty in the irrigated garden scenario was also dominated by the drinking-water consumption rate. This pathway accounted for essentially all of the uncertainty associated with iodine-129, selenium-79, cesium-135, and neptunium-237, and it was the major contributor (greater than 70%) for all other radionuclides. The only other parameters that contributed to total uncertainty for individual radionuclides were consumption of root vegetables for technetium-99 (5%), parameters related to external exposure from contaminated soil for tin-126 (25%), and parameters related to inhalation of resuspended soil for uranium-235 (less than 1%). Greater than 95% of the total dose uncertainty for all radionuclides can be attributed to these parameters.

The sensitivity analysis for the river scenario evaluated uncertainty in dose to the collective population, as opposed to individuals in the other cases. Because the dose is directly proportional to the number of exposed people, parameters related to the size of the population were not considered in this case. The set of radionuclides considered was the same as for the irrigated farm scenario and parameters that controlled uncertainty in the total dose were similar. Drinking water consumption controlled the uncertainty for neptunium-237 and selenium-79, accounting for 67% and 100% of the total, respectively. The irrigation rate for leafy vegetables also contributed to the total for neptunium-237. Parameters related to

animal product ingestion accounted for the major uncertainties for the other radionuclides, but only accounted for 30% to 70% of the total uncertainty in the effective dose equivalent.

4.2.4 Intruder Scenario Dosimetry

For the intruder scenarios, uncertainties in the quantity of grout brought to the surface, the area over which the grout is distributed, and the initial concentrations of significant radionuclides in the grout controlled the uncertainty in the total dose. Cesium-137 dominated the dose at 100 and 300 years after disposal; tin-126 was the most significant radionuclide at 500 and 1,000 years after disposal. Uncertainty in the duration of external exposure to soil containing the exhumed grout also contributed substantially to the total dose uncertainty, but was less important than the other parameters. In the post-drilling scenario, uptake of radionuclides by plants at early times and the quantity of soil resuspended and inhaled at later times after disposal made minor contributions to the total uncertainty. For both scenarios, at all times, these parameters accounted for 88% to 96% of the total uncertainty in the effective dose equivalent.

4.2.5 Sensitivity to Inventory

The sensitivity inventories of key radionuclides for groundwater scenarios are described in Section 3.6.5.6. The release of contaminants to the water table is directly proportional to the disposal inventory. If the number of vaults and site configuration are not changed, the concentration at a downgradient well is also proportional to inventory. However, if the inventory change involves a change in the number or layout of the grout vaults, the impact at a downgradient well will not be directly proportional because of changes in the amount of mixing occurring at the well intercept, as discussed in Section 4.2.2.

For groundwater scenarios, the only important radionuclides from a dose standpoint are iodine-129, technetium-99, and neptunium-237. In the central sensitivity case, the iodine-129 and technetium-99 dominate the initial plateau and the sharp peak that occurs after degradation of the asphalt barrier. The final long-term plateau is dominated by neptunium-237.

The sensitivity cases provide inventory estimates for key radionuclides that are substantially larger than the inventory used in the analysis. The impact of the largest sensitivity inventories can be illustrated by calculating the dose for the central sensitivity case at several points in time. The doses are provided in Table 4.7 for the times where maximums were obtained in the central sensitivity case simulation. These maximums were shown in Figure 4.22 and consist of an initial plateau, a sharp peak resulting from asphalt barrier degradation, and a final plateau. The times of the maximums are directly from the central sensitivity case without an additional analysis to determine changes in the time of maximum impact as the result of the inventory changes. The effect of simultaneously taking the high sensitivity case inventories

Table 4.7. Impact of Maximum Inventory Sensitivity Case on Dose for the Central Sensitivity Case Farm Scenario

Isotope	Base Inventory (Ci)	Sensitivity Inventory (Ci)	First Plateau (mrem/yr at 21,700 yr)	Sharp Peak (mrem/yr at 101,000 yr)	Final Plateau (mrem/yr at 2.58×10^5 yr)
^{129}I	14.6	46.4	3.7	15	3.7×10^{-5}
^{99}Tc	6,310	21,960	6.3	43	0.57
^{237}Np	53.7	56.1	1.2×10^{-6}	0.23	3.7
Total Dose ^(a)			11	58	4.2

- (a) The total doses in the central sensitivity case (Case 2.0) at each of these peaks were 3.0, 17, and 3.9 mrem/yr. The fraction of the total dose attributed to the three radionuclides was 1.000, 0.997 and 0.935. The totals in the table and percent change in the text following are calculated based only on these three key radionuclides.

of the three radionuclides of interest is that the initial plateau and the sharp peak at barrier degradation are increased by a factor of approximately 3.3 and 3.7, respectively. The long-term peak is less affected and is increased by only 10%.

Sensitivity inventories for the intruder scenarios are described in Section 3.6.5.6. For inventory sensitivity in the intruder scenarios, the distribution of the inventory between vaults is more important than the total inventory. The important radionuclides are cesium-137, tin-126, and americium-241. Technetium-99 and plutonium-238 contribute less than 2% of the total dose and are not considered in the intruder dose sensitivity. The sensitivity cases identified for the intruder scenarios include a value for cesium-137 based on the radionuclide heat load limit for the grout, and a value for americium-241 based on the 100-nCi/g processing limit on transuranic content for the waste. The current inventory value for tin-126 is already believed to be very conservative and the only sensitivity to this species was the use of the integrated data base value for tin-126, which is approximately a factor of 10 lower.

The sensitivity to inventory in the intruder scenarios is summarized in Table 4.8. In both the drilling and post-drilling habitation scenarios, only changes in cesium-137 are important at 100 years. At 500 and 1,000 years tin-126 is the most important radionuclide and reductions in this inventory significantly reduce the dose. If the tin-126 inventory is held at its base value (higher than its sensitivity case), adopting both the increased inventories for cesium-137 and americium-241 causes the dose to slightly exceed the 500-year, 100-mrem/yr performance objective in the post-drilling habitation scenario (1.1×10^2). This performance objective is not violated if the tin-126 sensitivity is simultaneously adopted. At

Table 4.8. Sensitivity to Inventory for Drilling Intrusion and Post-Drilling Habitation Scenarios

Sensitivity Inventory	Drilling Scenario (mrem) ^(a)			Post-Drilling Habitation Scenario (mrem/yr) ^(b)		
	100 yr	500 yr	1,000 yr	100 yr	500 yr	1,000 yr
Base Inventory	2.9×10^3	8.4	7.8	2.4×10^4	72	66
¹³⁷ Cs ^(c)	8.2×10^3	8.9	7.8	6.8×10^4	76	66
²⁴¹ Am ^(d)	2.9×10^3	11	9.0	2.4×10^4	1.0×10^2	79
¹³⁷ Cs and ²⁴¹ Am Sensitivity ^(e)	8.2×10^3	12	9.0	6.8×10^4	1.1×10^2	79
¹²⁶ Sn Sensitivity ^(f)	2.9×10^3	1.8	1.2	2.4×10^4	19	13

- (a) Performance objective is 500 mrem at 500 years. See Section 1.5.
- (b) Performance objective is 100 mrem/yr at 500 years. See Section 1.5.
- (c) Cesium-137 sensitivity inventory is a factor of 2.8 increase to represent the radionuclide heating limit for the grout.
- (d) Americium-241 sensitivity inventory is a factor of 5.6 increase to represent the maximum amount possible to meet the 100 nCi/g TRU limit on waste.
- (e) Results calculated with both cesium-137 and americium-241 at their sensitivity values.
- (f) Tin-126 sensitivity inventory is a factor of 10[>] decrease to represent Integrated Database estimate.

1,000 years, tin-126 becomes relatively more important due to decay of cesium-137 and americium-241, representing 94% and 89% of the dose in the drilling and post-drilling habitation scenarios, respectively.

4.3 Interpretation of Results

The majority of the activity in the waste to be disposed of in grout is associated with radionuclides (particularly cesium-137) with relatively short half-lives. These radionuclides are effectively contained within the engineered system and decay to negligible levels without reaching the accessible environment. However, some radionuclides with significant dose impacts have extremely long half lives (for example, 16 million years for iodine-129). For these radionuclides, the question is not whether the nuclide will eventually escape the engineered disposal system but instead what will be the timing and rate of the release. While intact, the engineered system does an excellent job of preventing transport of contaminants out of the engineered system. The ability of the engineered system to prevent release is decreased as the engineered system degrades over time. However, the results indicate that, even with assumed degradation, the performance objectives are still met in almost all cases. In a single case the drinking-water dose from a low-volume well exceeded the programmatic performance objective of 4 mrem/yr at

10,000 years. There is significant uncertainty in the long-term degradation of the engineered system over time. The system is expected to degrade very slowly with possible sudden changes due to severe seismic events. The conceptual model of degradation is important in determining the results obtained in the analysis. Due to the uncertainty, a conservative approach to the degradation has been taken to provide reasonable assurance that performance objectives will be met.

The analyses performed as part of this performance assessment required a large number of inputs in the form of data and assumptions to complete the calculations. This section discusses the uncertainties in the analysis and the conservatism that have been adopted. The nature of the data input and assumptions must be considered, along with the result of the calculations, to provide reasonable assurance that the performance objectives will be met.

4.3.1 Initial Physical Properties

In setting the initial physical properties for the grout disposal system, a mixture of data and assumptions were used. The physical properties are discussed for each media in which they occur.

4.3.1.1 Grout

The hydraulic conductivity and moisture retention properties for grout were measured on a grout produced using pilot-scale equipment with a nonradioactive chemical simulant for double-shell slurry feed (DSSF) waste. The dry blend mixture for the grout has since been changed and could potentially change again for each tank grouted to optimize the grouting process. Laboratory measurements of hydraulic conductivity support a value of 1.5×10^{-8} cm/s. This value is used in the sensitivity cases. An initial value of 1×10^{-10} cm/s was used in the compliance cases and this value is then degraded to a value of 1.5×10^{-6} cm/s over time. The effect of the grout hydraulic conductivity is relatively small while the engineered system is of high integrity. The water retention properties of the grout were measured using thermocouple psychrometry, and there is some uncertainty regarding the water retention properties because adjustments were made for the vapor depression resulting from the high salt content of the waste. However, sensitivity studies have indicated that the results are only moderately sensitive to increases in the hydraulic conductivity of the grout. The model is sensitive to decreases in hydraulic conductivity after the barriers degrade, but in the case of a decrease from the assumed value the effect is to decrease the impacts.

The diffusivity in the grout is selected to account for degradation caused by high-temperature curing. The effective diffusivities of the contaminants are placed in transport groupings that lead to conservatism for some species. Sorption coefficients are then calculated from the effective diffusivities. For iodine-129 and technetium-99, there is sufficient leach data on which to establish the mobility within the grout. However, for neptunium-237 data are not available for Hanford grout. Therefore, the grout distribution coefficients for the grout have been selected to be very conservative. Data in the literature indicate a distribution coefficient of 2,000 ml/g are likely (Höglund et al. 1985). The value selected for this

analysis was 125 ml/g. Use of 2,000 ml/g would be expected to greatly reduce the predicted impact of neptunium-237. Additional detail on available neptunium-237 sorption data is provided in Appendix P, Section P.2.1.

4.3.1.2 Concrete

The initial water retention and hydraulic conductivity for the concrete was measured on concrete samples that differ from the concrete in the vault. The initial hydraulic properties used for the concrete are believed to be reasonable. However, if the actual concrete properties were to differ significantly from those assumed, the impact would be seen only at early time frames prior to the assumed degradation of the concrete and asphalt barrier. The diffusivity value used for the concrete is believed reasonable for the most mobile species. No sorption is assumed in the concrete, a conservative assumption for species that are sorbed in the grout such as technetium-99 and neptunium-237.

4.3.1.3 Asphalt Barrier

The initial diffusivity for contaminants in the asphalt barrier is well supported by data in the literature as well as by experimental data collected for the Hanford Grout Disposal Program. The initial asphalt diffusivity value used in the compliance cases was derived from nitrogen permeability data without correction for the viscosity difference between nitrogen and water or the hydrophobic surface properties of the asphalt. This treatment is believed to be very conservative for intact asphalt. The asphalt barrier is also assumed to be initially cracked at the upper corners of the vault. These cracks may not occur, may require an extended time to develop, or may be self-healing since the entire system is in compression. The cracks are assigned the hydraulic properties of backfill soil to prevent the assumptions about the crack hydraulic properties from preventing release. It is possible that the cracks may remain empty with hydraulic properties that diminish the significance of flow through the cracks. For the purpose of vapor diffusion calculations, the crack is treated as being empty since this assumption is the more conservative treatment for water vapor diffusion. The approach to the assumptions regarding cracking was shaped by a desire to avoid meeting performance objectives through overly optimistic predictions of the performance of the barriers.

4.3.1.4 Soil Properties

Assumptions about individual soil properties are based primarily on data taken on samples obtained from a well drilled at the grout site. The stratigraphy is supplemented by additional data from wells in the surrounding area. The soil properties used here are believed to reasonably represent the properties of the soils beneath the disposal vaults. Sensitivity cases performed to examine the effect of the vadose zone indicated that the primary effect is to provide a delay before radionuclides reach the accessible environment, especially for neptunium-237. The distribution coefficient for neptunium-237 in the soils was taken as 3.0 ml/g, while information based on work on 200 West area sediments indicates a value of 10 to

20 ml/g would be justified (Sheppard, Kittrick, and Hardt 1976, Seme et al. 1993). Use of the larger distribution coefficient would have a significant beneficial effect on the timing and magnitude of the neptunium-237 doses. No sorption is assumed for technetium-99 or iodine-129, as a conservative treatment.

4.3.2 Recharge

The recharge rate assumed for the grout disposal site was 0.1 cm/yr. This assumption represents a conservative estimate for the recharge through the Hanford barrier. In fact, 0.1 cm/yr is the estimated recharge without a Hanford barrier. In addition to the 0.1-cm/yr case, the potential effects of 5.0-cm/yr recharge and 0-cm/yr recharge through the grout site to an inhabitant have been analyzed.

4.3.3 Unknown Future/Degraded Properties

The greatest uncertainty associated with this performance assessment involves the prediction of the long-term future of the vault system. It is this area of uncertainty that prevented a consensus on a single best estimate case for the long-term performance of the disposal system. Because of this uncertainty, we attempted to formulate a conservative treatment for degradation of the disposal system. In addition, the impact of possible changes that could occur in the future have been analyzed, including a glacial flood and a climate change that increases recharge to 5.0 cm/yr.

Sensitivity cases indicated that the performance of the system is sensitive to the assumptions about cracks in the asphalt barrier and concrete vault. This information has been taken into account in the definition of compliance cases. Cracks are placed in the upper corners of the asphalt barrier after 100 years. Additional degradation of the vault system is assumed to occur at fixed time intervals. The asphalt is assumed to biodegrade from the edges of the barrier and within cracks at a rate of 1×10^{-3} cm/yr; the measured value of biodegradation of irradiated AR-6000 asphalt in 70% saturated Hanford soil at ambient temperature over 310 days is 1.0×10^{-4} cm/yr (Luey and Li 1993). The rate of degradation was greater than 1×10^{-3} cm/yr in the compliance cases. Seismic events, rebar corrosion, and minor differential settling contribute to possible cracks in the asphalt barrier, concrete, and grout. At 5,000 years the barrier and concrete vault were modeled to experience generalized cracking that significantly reduces their effectiveness. Between 5,000 and 40,000 years the grout, concrete, and asphalt reach a severely degraded state. The changes are modeled as being sudden and occurring simultaneously. Actual changes may be gradual over time and not all of the vaults are likely to degrade at the same rate. Different rates of vault degradation would tend to smooth the peaks and reduce the maximum doses calculated.

It is believed that there is a reasonable expectation that the degradation modeled is greater than that which will actually occur. However, the conservatism in the treatment is warranted by the uncertainty regarding long-term properties of the system.

4.3.4 Inventory

The results of the performance assessment are directly related to the inventory of important radionuclides disposed of in grout (iodine-129, technetium-99, and neptunium-237 for the groundwater pathway). The current projected radionuclide inventory (total Ci values in Table 2.4) is based on analyses of wastes to be grouted directly, and on estimates based on projected separations for wastes that must be treated before they are grouted. The uncertainty of iodine-129, technetium-99, and neptunium-237 in the inventory of the waste volume currently planned for grouting could increase dose through the groundwater pathway by as much as a factor of 3.7.

Changes in inventory of other radionuclides cannot credibly change the groundwater-related doses for the current disposal plans. The level of uncertainty in the inventory will be reduced as additional tanks are analyzed and processed. Future changes in the disposal plans could also increase or decrease the inventory of key radionuclides to be disposed of in grout.

4.3.5 Groundwater

Unlike travel time in the vadose zone, travel time in the saturated zone is relatively short and therefore unimportant in the analysis. However, because the performance objectives are closely linked to the concentration of radionuclides in the well, the amount of mixing of contaminated recharge in groundwater is a factor in the analysis. In addition, the manner in which a well is completed will influence the concentrations seen in the well. The highest well concentrations will be seen for a short well screen near the top of the saturated zone. The well construction selected was a 4.6-m well screen at the top of the saturated zone consistent with monitoring well practices at Hanford. Contaminated recharge was assumed to be mixed into the groundwater to a depth of 4.6 m, which, for a low volume well, is equivalent to an assumption that the contamination is mixed with the groundwater over the screened interval of the well. For higher pumping rates consistent with irrigation, a well intercept analysis was performed. This analysis determined that over half of the contaminant plume would be intercepted by the well.

The use of a 4.6-m screened interval well placed in the center of the plume is conservative. Actually, an irrigation well screen would likely be placed deeper in the aquifer to ensure an adequate supply of water. Also, such a well might not be positioned to maximize the intercept of contaminated water. However, by assuming a 4.6-m screen on a well centered in the plume, the result is conservative.

4.3.6 Exposure Scenario Dosimetry

There is uncertainty with the formulation of exposure scenarios. To account for this uncertainty, a number of different scenarios are postulated that are formulated to be relatively conservative while still realistic. Based on these scenarios, an analysis of the uncertainty in the dosimetry was performed. The uncertainty in the farm, garden, and drinking-water scenarios is largely controlled by the consumption rate of drinking water. The conversion from a concentration in drinking water to the resulting dose is performed using widely accepted dose conversion factors. However, the uncertainty in these conversion

factors is a factor of 10 or more. Actual doses from individual radionuclides could be higher or lower than those currently calculated. To avoid confusion, the widely accepted conversion factors have been used.

4.3.7 Climate Uncertainty

As discussed in Chapter 2, the climate is expected to remain relatively constant over the next 5,000 to 10,000 years. Over the 1,000,000 years modeled in this performance assessment, more dramatic climatic changes are anticipated. The impacts of these changes have been addressed through analyses of higher recharge rates to the soil corresponding to increased precipitation, and through consideration of a "catastrophic" flood that would distribute the inventory over some region larger than the Grout Disposal Facility. The timing of catastrophic natural events becomes significant when the event occurs before complete degradation of the engineered disposal system. Aside from the obvious devastating effects, a catastrophic flood would actually reduce the doses from disposal of wastes in grout on the Hanford Site.

5.0 Performance Evaluation

This performance assessment documents the potential radiological impacts to the public and the environment from the disposal of grouted low-level radioactive wastes stored in double-shell tanks at the Hanford Site. It estimates the impacts of the disposal action and compares the results to performance objectives outlined in DOE orders. This chapter summarizes the results from Chapter 4 and compares them to the performance objectives described in Chapter 1. It also provides recommendations for design changes that could enhance the performance of the engineered grout disposal system and suggests data needs and research that would reduce uncertainties and conservatisms in the performance assessment analyses, thereby increasing confidence in the results.

5.1 Comparison to Performance Objectives

The performance objectives for the disposal of grouted low-level radioactive wastes stored in double-shell tanks at the Hanford Site are derived from DOE Order 5820.2A (U.S. DOE 1988a) and DOE-RL Order 5820.2A (U.S. DOE-RL 1990), and applicable federal, state, and local regulations as described in Chapter 1. The performance objectives focus on protection of 1) the general public, 2) inadvertent intruders into the disposal site, and 3) the groundwater resource. Although the DOE-RL Order specifies 1,000 years, the Hanford Grout Disposal Program has adopted 10,000 years as the performance objective for protection of the general public and the groundwater resource. Comparison of the grout disposal system performance to each of these objectives is addressed below.

5.1.1 Protection of the General Public

The performance objective for protection of the general public is to provide reasonable assurance that the maximum radiation dose to any member of the public does not exceed 25 mrem/yr for 10,000 years after disposal. Beyond that time, exposures are to be as low as reasonably achievable (ALARA) such that the peak collective dose to the exposed population is less than 500 person-rem/yr. In addition, radon release rates to the atmosphere from waste storage and disposal facilities are to be less than 20 pCi/m²-s. In this performance assessment, exposures to the public are postulated to occur through the use of groundwater for farming/gardening or through use of the Columbia River.

Table 5.1 shows the results from the compliance cases. The regulatory (1,000 years) and programmatic (10,000 years) performance objectives to limit doses to less than 25 mrem/yr are met. Beyond 10,000 years, the estimated doses in the irrigated garden groundwater scenario exceed 25 mrem/yr. However, the 500-person-rem/yr performance objective is the applicable objective at these times, and this objective is met. Radon emissions from the disposal site will be within limits. All performance objectives related to protection of the general public, as defined in DOE Order 5820.2A and DOE-RL Order 5820.2A, are met by the planned disposal of grouted low-level waste.

Table 5.1. Comparison to Performance Objectives for Protection of the General Public

Performance Objective	Exposure Path	Estimated Dose or Flux ^(a)	
25 mrem/yr up to 10,000 yr	Groundwater, irrigated farm	<0.01 mrem/yr at 1,000 yr ^(b)	0.28 to 5.2 mrem/yr at 10,000 yr ^(b,c)
25 mrem/yr up to 10,000 yr	Groundwater, irrigated garden	<0.01 mrem/yr at 1,000 yr ^(b)	0.47 to 8.2 mrem/yr at 10,000 yr ^(b,c)
20 pCi/m ² -s	Radon emission in air	8 pCi/m ² -s	
ALARA - 500 person-rem/yr ^(d)	Columbia River	<0.1 person-rem/yr ^(e)	
ALARA - 500 person-rem/yr ^(d)	Groundwater, community well	2.0 to 2.8 person-rem/yr ^(b,c,e)	

(a) Incremental increase.

(b) Maximum doses occur at end of indicated time period.

(c) Estimated doses shown span range covered by compliance cases modeled.

(d) For all times up to the year of maximum impact.

(e) In year of maximum impact.

5.1.2 Protection of Inadvertent Intruders

DOE Order 5820.2A provides performance objectives for the protection of intruders who "inadvertently may intrude into the facility after the loss of active institutional control (100 years)." The Order provides a limit of 100 mrem/yr for continuous exposure and 500 mrem for a single acute exposure. DOE-RL Order 5820.2A provides additional guidance for the Hanford Site. It specifies that for wastes that may exceed the 100-mrem/yr or 500-mrem intruder limits beyond 100 years, passive controls are to be included in the disposal system to deter intruders for up to 500 years.

Because the grouted waste will exceed the intruder dose limits after the 100-year active institutional control period, passive controls are incorporated in the disposal system to warn and deter potential inadvertent intruders. The grout will be disposed at a minimum 5-m depth below grade. In addition, to warn of the potential hazard, the disposal site will include markers such as peripheral granite monoliths plus several layers of warning discs emplaced in the permanent isolation barrier above the waste zone. The

riprap layer in the permanent isolation barrier, the asphalt barrier, and the reinforced-concrete vault will all act to deter intrusion. These measures are assumed to effectively prevent inadvertent intrusion for at least 500 years. Therefore, the dose impacts for intruder scenarios are compared to performance objectives at 500 years.

It is expected that drilling, either for a water well or mineral exploration, would be the most likely form of inadvertent intrusion. Because the grout will be at least 5 m below grade, it would not be reached during excavation for a residential basement. Therefore, intrusion during excavations was not considered a plausible exposure scenario. The scenarios used in this performance assessment involve a single acute exposure to a driller who drills directly through the grout, as well as the chronic dose to an individual who grows a garden in soil contaminated by waste brought to the surface during drilling.

The doses for the two scenarios at 500 years are compared to the performance objective in Table 5.2. Based on the analyses performed for the intruder scenarios, there is reasonable assurance that the doses to inadvertent intruders will be within the performance objectives of 500 mrem for a single acute exposure and 100 mrem/yr for chronic exposure at 500 years.

5.1.3 Protection of the Groundwater Resource

DOE Order 5820.2A requires protection of the groundwater consistent with federal, state, and local requirements, and DOE-RL Order 5820.2A specifies that the dose from radionuclide concentrations in the groundwater should not exceed an effective dose equivalent of 4 mrem/yr to an individual drinking 2 L/d from the aquifer. Although the DOE-RL Order specifies 1,000 years, the program has adopted 10,000 years as the time period for the performance objective.

Table 5.3 shows the results of the groundwater protection analyses. Both radionuclide and chemical (nitrate) impacts are shown. The regulatory performance objective identified in DOE-RL Order 5820.2A for groundwater protection at 1,000 years is met by the grouted waste disposal action. The longer term, 10,000-year programmatic performance objective is achieved by all but one of the

Table 5.2. Comparison to Performance Objective for Protection of Intruders

Performance Objective	Exposure Path	Dose at 500 years
500 mrem	Drilling	8.4 mrem ^(a)
100 mrem/yr	Post-drilling habitation	72 mrem/yr

(a) Effective Dose Equivalent.

Table 5.3. Comparison to Performance Objective for Groundwater Protection

	Performance Objective	Estimated Dose or Concentration	
		1,000 yr	10,000 yr
Radionuclides	4 mrem/yr up to 10,000 yr	<0.01 mrem/yr	0.42 to 6.9 mrem/yr
Nitrates (as N)	10 mg/L up to 10,000 yr	<10 ⁻¹⁰ mg/L	6.1 mg/L

compliance cases evaluated in this performance assessment. In the one compliance case, there is sudden drainage from the vault roof associated with the degradation of the roof. This drainage is not observed in the other compliance cases because those cases more realistically include drainage paths associated with the cover block joints. At the time of maximum impact beyond 10,000 years, doses from drinking groundwater are above 4 mrem/yr.

The analyses of the compliance cases are believed to be conservative, particularly with respect to timing and rate of degradation of the engineered system. Biodegradation was modeled to consume the asphalt in only 40,000 years as opposed to a projected 420,000 years, based on measured biodegradation rates. The majority of cases included the development of patterned cracks in the asphalt barrier after only 5,000 years. Technical experts indicate that such a high degree of cracking is not expected until sometime in the 10,000- to 100,000-year time period. The lowest all-pathways and drinking-water doses at 10,000 years shown in Tables 5.1 and 5.3 are for the delayed degradation compliance case in which patterned cracking does not occur until 10,000 years. As more data become available with which to reduce the uncertainties and conservatism in the analyses, we expect that all estimates of 10,000-year groundwater impacts will meet the performance objectives established for the Hanford Grout Disposal Program.

5.2 Changes to the Design of Future Grout Disposal Systems

This performance assessment shows that the grout, the asphalt barrier, and the gravel layer play important roles in the performance of the engineered disposal system. Several design changes to enhance the performance of the engineered disposal system are suggested by the results of this performance assessment. Because advection through the grout is the most significant release mechanism, these design changes focus on minimizing advection by diverting infiltration away from the vault and barrier, minimizing the potential for through-wall cracks in barriers and thus minimizing continuous advection pathways, and reducing the hydraulic conductivity of the grout. Additional analyses are required to demonstrate and quantify the benefits of the proposed changes.

The gravel layer between the Resource Conservation and Recovery Act (RCRA) cover and the top of the meter-thick asphalt barrier plays a key role in the performance of the system. The gravel acts as a capillary break and diverts infiltrating water that would otherwise impinge directly onto the asphalt

barrier. Making the gravel layer thicker should reduce any existing potential for the gravel layer to be significantly degraded by the movement of fine soils into the open porosity of the gravel. Extending the gravel and RCRA cover laterally well beyond the edge of the asphalt barrier should divert infiltrating water beyond the influence of any cracks that may develop in the upper corner region of the asphalt barrier. This region is believed to be a likely location for cracks to develop. To mitigate the effects of potential cracks, gravel could be wrapped vertically around the upper corners of the asphalt barrier to minimize water infiltration into any cracks in this region of the structure. A vertical gravel-filled trench could be added at the ends of the gravel to ensure that vertical infiltration of diverted water would occur well away from the asphalt barrier.

Cracks are projected to form at the top corners of the asphalt barrier because of settlement and creep of the barrier as it fills the space initially occupied by the thermal insulation board between the asphalt barrier and the concrete vault. The insulation board is required to protect the vault from thermal stresses. It is composed of wood fiber and is susceptible to long-term degradation and disintegration. The potential for substituting another material with equivalent thermal properties and a lower potential for degradation should be studied. Gravel or asphalt-coated gravel may provide the necessary thermal protection for the vault and would also provide long-term structural stability. Such a design modification would greatly reduce the potential for the asphalt barrier to slump, creep, and crack during the first few thousand years.

In this performance assessment, the grout is modeled as having an initial saturated hydraulic conductivity of $1 \times 10^{-10} \text{ cm}^2/\text{s}$, which is then degraded in steps to $1.5 \times 10^{-6} \text{ cm}^2/\text{s}$ over 20,000 years. This treatment is probably conservative and better data on the grout hydraulic conductivity are needed. Also, through the grout formulation development efforts, it may be possible to reduce the hydraulic conductivity by several orders of magnitude. For example, the saltstone waste form used at DOE's facility at Savannah River has been modeled with a saturated hydraulic conductivity of $1 \times 10^{-11} \text{ cm/s}$. Changing such a property of the grout could be accomplished by changing and testing the grout formulation. Changing the formulation may require modifications to the Grout Processing Facility to process a denser, more viscous slurry. A greater solids-to-liquid ratio implies that the volume of grout and number of vaults would increase to dispose of the same volume of waste.

5.3 Data and Research Needs

This section describes the additional research and data collection that may be performed to reduce the uncertainties and conservatisms in the performance assessment analyses. Pursuing this work is consistent with the concept that the performance assessment is a "living" document to be maintained and revised as additional information becomes available.

5.3.1 Neptunium Sorption

Neptunium-237 is a key radionuclide that, in the compliance cases analyses, is the primary contributor to dose in groundwater scenarios after 100,000 years. Unlike the other key radionuclides, a Hanford-specific data set on which to base the mobility of neptunium in the grout and soil does not exist. The distribution coefficients of 125 ml/g in the grout and 3 ml/g in the soil are conservative estimates based on the general literature. In actuality, the expected distribution coefficients are 10 to 20 ml/g in the soils and 1,000 to 6,000 ml/g in the grout. Obtaining specific distribution coefficients for the grout and soil could substantially reduce the impact of neptunium-237 and greatly reduce the calculated doses at times greater than 100,000 years.

5.3.2 Technetium Release

Unlike neptunium-237, a substantial amount of data on the release of technetium-99 from Hanford-specific grout have been obtained using a leach test configuration. The current sorption coefficients for technetium-99 are derived from the behavior observed in leach tests relative to more mobile species such as nitrate. Although this approach is believed to be valid, technetium-99 is an extremely important isotope in terms of its contribution to doses in the performance assessment. Because of the importance of technetium-99 and the advective rather than diffusive nature of the modeled release, additional data in which the grout pore solution concentration of technetium-99 is directly measured over a range of waste loadings would be useful.

5.3.3 Timing and Magnitude of Degradation

One of the greatest uncertainties in the performance assessment analysis is the degradation of the engineered disposal system. The degradation estimates include predictions of the timing and magnitude of cracks in the asphalt, concrete, and grout as well as predictions of the transport properties of the materials in their degraded states. It is difficult to predict the timing and magnitude of cracks over time (i.e., when and where do cracks form, what are the differences in their orientation, size, interconnectedness, etc.). It is also difficult to predict the extent to which cracks in the grout and concrete would tend to plug as a result of precipitation of solids within the cracks. In addition, the natural overburden pressure may tend to close cracks over time. Because of the uncertainty in this area, a conservative approach has been taken to modeling the degradation of the engineered system. Additional research to better define the degradation of the engineered system over time may permit a more realistic treatment of degradation, in turn permitting some conservatism to be removed from the model.

5.3.4 Hydraulic Properties of Grout and Concrete

Although the hydraulic properties of the grout and concrete are degraded over time in a conservative manner, additional data are needed to support the initial, intact hydraulic properties of the grout and concrete. The grout hydraulic conductivity used in the compliance cases was based on scoping tests and

needs to be confirmed. The water retention properties and hydraulic conductivity used here for the concrete may not accurately represent the actual concrete placed during vault construction.

5.3.5 Hydraulic Properties of the Asphalt Barrier

Hydraulic properties assigned to the original asphalt barrier also have a significant impact on the dose predictions for times preceding substantial degradation of the asphalt barrier (e.g., through-wall cracking and biodegradation). In the sensitivity studies, the hydraulic conductivity of intact asphalt was arbitrarily set at 1×10^{-20} cm/s to prevent advection within the intact barrier material. The intact barrier material is hydrophobic and has low permeability. Therefore, advection of water under unsaturated conditions in this media is not expected. When simulated using a saturated hydraulic conductivity of 1×10^{-11} cm/s (corresponding to the nitrogen permeability) and simulating the asphalt volume as water, the doses were increased by 70% in the period preceding final asphalt degradation. The hydraulic conductivity extrapolated from nitrogen permeability studies represents an upper bound on the properties of the intact barrier. This value has not been adjusted for the viscosity of water nor for the hydrophobic nature of the asphalt. Gathering the data needed to support these adjustments would reduce the impact occurring at earlier times as a result of advection in the asphalt barrier.

If the asphalt cracks or degrades but the degraded material has a lower affinity for water than do surrounding soils, the degraded asphalt barrier could still serve as an effective barrier to advection through the engineered system. If additional research can establish the degraded properties of the asphalt barrier, the data may allow some credit to be taken for the extremely long-term influence of the asphalt barrier. Currently, the asphalt barrier is modeled to be completely degraded and is assigned the properties of backfill soil after 50,000 years.

5.3.6 Hydraulic Properties of Gravel Layer

In this performance assessment, the behavior of the gravel layer above the vault is important to the final result. The gravel layer forms a capillary break with overlying filter sand, diverting recharge that would otherwise enter cracks assumed to be present in the asphalt barrier and concrete. The hydraulic properties of the filter sand and gravel should be measured and experiments conducted to demonstrate the capillary break for the materials and infiltration rates being used in the performance assessment.

5.3.7 Waste Inventory

Characterization data for existing tank wastes and definition of separation process flowsheets are limited such that the final inventory of radionuclides to be disposed of as grouted low-level waste remains uncertain. Increases or decreases in inventory without a change in the number or arrangement of vaults create a linear response in the dose estimate. The impact of changes that alter the number of vaults is less than proportional. The characterization data for existing tank wastes reflect the wastes to be disposed of in the first vaults. Thus, the actual complete inventory for grout disposal will not be well known until all

wastes are characterized and flowsheets are better defined. The existing low-level wastes are being characterized and the concentrations are within the bounds of the inventory analyzed in this performance assessment. As additional wastes are characterized and flowsheets are defined, the impacts on the projected inventory will be addressed in updates to this performance assessment.

5.3.8 Additional Modeling

As additional data describing the initial and degraded properties become available, the data need to be incorporated into the model to establish their effect on the final dose estimate. Currently, additional modeling work that could be performed includes an additional compliance case simulation that examines the effect of placing the gravel wedge over a pair of vaults (as in the current design) rather than over a single vault as is currently modeled. This treatment may reduce release. Also, the effect of placing a water vapor diffusion source over the entire vault (rather than in the upper regions only) might be investigated. In addition, other parameters that might be adjusted to represent more easily defended values without significantly affecting doses would be the diffusivity in the gravel wedge and the initial grout saturated hydraulic conductivity. In addition, the line of low conductivity cells included in some compliance cases could be removed or degraded over time.

5.4 Conclusion

DOE Order 5820.2A requires that "field organizations with disposal sites shall prepare and maintain a site-specific radiological performance assessment for the purpose of demonstrating compliance with performance objectives . . ." The performance objectives are prescribed in the Order and in DOE-RL Order 5820.2A. The performance objectives for the Hanford Grout Disposal Program are to

1. protect the general public such that the maximum dose to an individual from all pathways does not exceed 25 mrem/yr for up to 10,000 years
2. protect intruders through warning systems and limited inventory such that they receive no more than a maximum single acute dose of 500 mrem or a continuous dose of 100 mrem/yr
3. protect the groundwater resource for up to 10,000 years such that an individual consuming the groundwater at 2 L/d would receive a maximum dose of no more than 4 mrem/yr.

To meet these performance objectives, the Hanford Grout Disposal Program has designed a disposal system composed of a cementitious grout waste form, reinforced-concrete vaults to contain the grout, an asphalt barrier surrounding the grout/vault structure, and surface barriers with warning markers to control infiltration and deter intrusion into the disposal area. This assessment evaluates the performance of the engineered disposal system, being conservative in approach in order to account for uncertainties. This performance assessment provides a reasonable assurance that the disposal system will meet the performance objectives for disposal of low-level double-shell tank waste on the Hanford Site.

6.0 Resumes of Preparers

KATHY A. BLANCHARD, Technical Communications Specialist, Communications Department, Pacific Northwest Laboratory

B.A. English, Central Washington University 1982

Ms. Blanchard provides communications planning and writing and editing support to various programs in PNL's Waste Technology Center. She is responsible for editing the performance assessment and overseeing the document production tasks.

KENNETH W. BLEDSOE, Principal Engineer, Grout Technology Section, Westinghouse Hanford Company

B.S. Geology, University of Washington 1960

Mr. Bledsoe has over 40 years of experience in the testing business in many different kinds of laboratories. His experience includes 25 years in the field of engineering materials testing. He has had extensive experience with portland cement products, asphaltic cement concrete, and soil mechanics. His past work includes many investigations into construction failures, and production of numerous mix designs for concretes, grouts, and mortars. Mr. Bledsoe is at present concerned with closure plans for the vaults and is responsible for the formulation and placement of the cold cap grout.

CHARLES R. COLE, Staff Scientist, Hydrology Section, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S. Physics, Kent State University 1964
M.S. Computer Science, Washington State University 1975

Mr. Cole has been a Staff Scientist at PNL since 1966. He has over 20 years of experience in groundwater flow and transport modeling, as well as the modeling of chemical, biological, and ecological systems. Mr. Cole has developed various 2- and 3-D flow and transport codes and is a recognized expert in groundwater modeling, with both national and international experience in nuclear waste management studies involving performance assessment.

JOHN M. CONNER, Engineer, Grout Technology Section, Westinghouse Hanford Company

B.S.	Chemical Engineering, California State Polytechnic University	1989
------	---	------

Mr. Conner has been with the Hanford Grout Disposal Program for over 3 years. He has worked on verification of grout quality, including core drilling of the first vault and development of nondestructive testing methods. He wrote the sampling plan for the Grout Treatment Facility. Mr. Conner helped coordinate responses to the Peer Review Panel comments on this performance assessment, and reviewed the performance assessment for compliance with regulatory and guidance documents.

MICHAEL J. FAYER, Senior Research Scientist, Hydrology Section, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Plant and Soil Science, University of Maine at Orono	1976
M.S.	Plant and Soil Science, University of Massachusetts, Amherst	1981
Ph.D.	Plant and Soil Science, University of Massachusetts, Amherst	1984

Dr. Fayer has 9 years of experience in unsaturated flow and transport studies, including performance assessment and protective barrier studies. His work includes laboratory measure of the hydraulic and geotechnical properties of uranium mill tailings; computer modeling of water, heat, and solute flow; and management of the Hanford Site Performance Assessment project for three years. His contribution to this performance assessment was his early involvement in analyzing the physical and hydraulic properties of sediments from well 299-E25-234 at the Grout Treatment Facility Site.

MARK D. FRESHLEY, Senior Research Scientist/Technical Group Leader, Geosciences Department, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Geological Sciences, University of Washington	1979
M.S.	Hydrology, University of Arizona	1982

Mr. Freshley has over 15 years of experience in both field and modeling studies in groundwater hydrology. His participation in field analyses consists of field characterization of groundwater for the Site-Wide Ground-Water Monitoring Project at the Hanford Site. In the modeling area, his work has focused on simulating the movement of water and contaminants in the unsaturated zone for the high-level nuclear waste study at Yucca Mountain, Nevada; predicting the movement of groundwater flow and contaminant transport in the unconfined aquifer at the Hanford Site; and reconstructing the movement of radionuclides in the atmosphere, surface water, and groundwater to estimate the potential dose from past Site emissions for the Hanford Environmental Dose Reconstruction Project.

DOUGLAS W. HENDRICKSON, Senior Engineer, Grout Facilities Engineering Section, Hanford Grout Disposal Program, Westinghouse Hanford Company

B.S.	Chemical Engineering, University of Texas	1984
M.S.	Chemical Engineering, Washington State University	In progress

Mr. Hendrickson has been the responsible engineer for Hanford double-shell tank waste sampling, characterization, scheduling, and optimization for the Hanford Grout Disposal Program. Mr. Hendrickson provided waste data accumulation and recommendations for this performance assessment.

WILLIAM E. KENNEDY, JR., Technical Group Leader, Environmental Health Physics Group, Pacific Northwest Laboratory

B.S.	Nuclear Engineering, Kansas State University	1973
M.S.	Nuclear Engineering, Kansas State University	1975

Since joining Pacific Northwest Laboratory in 1975, Mr. Kennedy has contributed to and led projects that require the practical application of information in the areas of radionuclide effluent characterization and environmental behavior, radiation dosimetry, safety assessment radiation shielding health physics, and statistical analysis. He has been involved in the development and application of environmental pathway and radiation dosimetry models used to assess the potential health and environmental impacts resulting from release of radionuclides to the environment. He has specialized in using these models to evaluate alternatives and predict health impacts from radioactive waste disposal, decommissioning of nuclear facilities, and nuclear facility operation.

CHARLES T. KINCAID, Staff Scientist, Geosciences Department, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Civil Engineering, Humboldt State College	1970
Ph.D.	Engineering (Hydraulics), Utah State University	1979

Dr. Kincaid is the technical manager and a key contributor to the Grout Performance Assessment task for the Hanford Grout Disposal Program. Prior to his assignment to this performance assessment activity, he was Technical Group Leader of the Soil Physics Group within the Hydrology Section at PNL. Before that he was Technical Group Leader of the Subsurface Transport Group. In the past decade he has been a key contributor in two major software development efforts involving contaminant transport codes for the

subsurface environment; one resulted in the development of a standard flow and transport software product, and the other involved the merging of flow, transport, and mechanistic geochemistry software. He has also contributed to other performance assessment studies, including the Hanford Defense Waste Environmental Impact Statement published in 1987.

DAVID W. LANGFORD, Senior Software Engineer, Boeing Computer Services Richland

B.S.	Physics, Washington State University	1976
M.S.	Physics, Montana State University	1980

Mr. Langford has 13 years of experience in developing and applying numeric models to problems in continuum mechanics. Principal applications include saturated and unsaturated groundwater flow and contaminant transport. He has applied both finite difference and finite element modeling techniques to a variety of problems.

BETTE G. LAUZON, Technical Writer/Editor, Boeing Computer Services Richland

B.A.	Journalism, University of Washington	1976
------	--------------------------------------	------

Ms. Lauzon's experience includes writing and editing safety analyses, safety assessments, and regulatory documents related to waste disposal and waste remediation. She assisted with the editing and production of this performance assessment.

FREDERICK M. MANN, Fellow Scientist, Environmental Risk and Performance Assessment (ERPA), Engineered Applications, Westinghouse Hanford Company

B.S.	Physics, Stanford University	1970
Ph.D.	Physics, California Institute of Technology	1975

Dr. Mann has 17 years of experience with the Westinghouse Hanford Company. Most of this experience has been with nuclear data and the modeling (including code development) of nuclear facilities with large computer codes. His contribution to this performance assessment included supervision of ERPA activities in groundwater flow and contaminant transport modeling as well as writing these sections.

MICKI McKINLEY, Technical Specialist II, Geosciences Department, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Environmental Resources Engineering	1992
	Humboldt State University	

Ms. McKinley chose water resources as the emphasis of her studies, with special attention to groundwater modeling. Her senior project involved the development of a user interface for MODFLOW, a USGS groundwater simulation model. Since beginning her employment with Battelle, she has worked intensively with the SLAEMS model.

GARY W. McNAIR, Manager, Waste Systems Department, Waste Technology Center, Pacific Northwest Laboratory

B.S.	Nuclear Engineering, Oregon State University	1976
M.S.	Nuclear Engineering, Oregon State University	1977
Ph.D.	Nuclear Engineering, Oregon State University	1982

Dr. McNair has 12 years of experience in hazardous and nuclear waste management projects. He has managed several research projects, including the performance assessment of a new technology to safely contain radioactive and hazardous waste, an ALARA-based transportation analysis to determine an effective design for a nuclear waste transport system, the development of a computer code to analyze cost/risk within transportation systems, and the development of an interface for a waste management system simulation code. Dr. McNair previously managed the Grout Performance Assessment Task, and contributed to the review of this performance assessment.

CLARENCE A. OSTER, Principal Software Engineer, Boeing Computer Services Richland

B.S.	Mathematics, University of Oregon	1957
M.S.	Mathematics, University of Oregon	1958

Mr. Oster has over 30 years of experience in numerical analysis and computer science. He participated in the development of a research code to simulate transport of contaminants in a porous media containing regions of diffusion-dominated transport and regions of advection-dominated transport. He currently is a member of a team applying existing codes to such problems. Mr. Oster conducted modeling and benchmarking/verification for this performance assessment.

KENNETH LEE PETERSEN, Principal Scientist, Environmental Technology and Assessment Group,
Westinghouse Hanford Company

B.A.	Anthropology, University of Utah	1970
M.A.	Anthropology, Washington State University	1975
Ph.D.	Anthropology, Washington State University	1981

Dr. Petersen has 25 years of experience in multi-disciplinary environment- and climate-related studies, including 10 years in managing, supervising, or coordinating large technical programs. He has experience in climate prediction, characterization, and reconstruction primarily using pollen but also other proxy climate records. Since 1988, he has coordinated the long-term climate change assessment task and the warning marker system for DOE's Hanford Protective Barrier Development Program. During 1987, he coordinated an investigation to characterize the past, present, and potential future climate of a DOE high-level nuclear waste repository at the Hanford Site. Between 1981 and 1985, he directed a team of environmental specialists and consultants who analyzed the botanical, faunal, and geological and soil specimens recovered from a Bureau of Reclamation archaeological mitigation project associated with dam construction in southwest Colorado to investigate the impact of climatic change on prehistoric inhabitants of the region.

MEL G. PIEPHO, Principal Engineer, Environmental Risk and Performance Assessment Section,
Westinghouse Hanford Company

B.S.	Mathematics and Physics, Butler University	1968
M.S.	Physics, Indiana University	1970
M.A.	Mathematics, Indiana University	1971
Ph.D.	Physics, Indiana University	1974

Dr. Piepho has over 20 years of mathematical modeling, numerical analysis, and computer science experience. For the last 10 years he has concentrated on studies of vadose zone flow and waste transport (both single and multiphase). He has previously performed flow and waste migration calculations for the Hanford Defense Waste Environmental Impact Statement and the High-Level Waste Yucca Mountain Project, which included flow in fractures. He modified PORFLOW specifically for this performance assessment; in particular, the degradation of flow and transport properties over time and flow/transport in fractures. He led and organized the flow and transport modeling effort at Westinghouse Hanford Company, and produced all of the vadose zone results for the performance assessment.

KATHLEEN RHOADS, Senior Research Scientist, Health Risk Assessment Department, Life Sciences Center, Pacific Northwest Laboratory

B.S.	Microbiology, University of Washington	1972
M.S.	Radiological Sciences, University of Washington	1979

Ms. Rhoads has been employed at Pacific Northwest Laboratory since 1975 in the Biology and Chemistry Department (1975-85), Materials Sciences Department (1985-88), Health Physics Department (1988-93), and Health Risk Assessment Department (1993-present). Her current responsibilities include risk assessment and estimation of radiation doses following routine or accidental release of radionuclides to the environment from nuclear facilities, and evaluation of health effects from energy production. Ms. Rhoads is a member of the Health Physics Society, the National Association of Corrosion Engineers, and is certified by the American Board of Health Physics.

MARK L. ROCKHOLD, Research Scientist, Geosciences Department, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Geology, Kansas State University	1984
M.S.	Soil Physics, Kansas State University	1988

Mr. Rockhold has over 5 years of experience in unsaturated flow and solute transport modeling related to performance assessment studies. He is currently involved in the development and testing of a multiphase flow and transport simulator that is being used in support of environmental remediation activities at various sites. He estimated the physical and hydraulic parameters that were used for flow and transport modeling and contributed to the verification and benchmark testing of the codes used in this performance assessment.

R. JEFF SERNE, Staff Scientist, Geosciences Department, Earth and Environmental Sciences Center, Pacific Northwest Laboratory

B.S.	Chemistry, University of Washington	1969
B.S.	Oceanography, University of Washington	1969

For the past 23 years, Mr. Serne has worked primarily in the areas of solidified waste-groundwater reactions, soil-waste water interaction, sediment-heavy metal sorption-desorption phenomena, and radioactive waste disposal processes. His work has involved developing mathematical predictor equations to evaluate the migration potential of contaminants and investigating, through laboratory experiments and field studies, the mechanisms of waste form leaching, sediment and soil-water ion exchange, and precipitation and sequestration of trace contaminants, with emphasis on radionuclides and regulated trace metals.

As part of the Hanford Grout Technology Program, Mr. Serne is performing laboratory studies to determine leach rates of contaminants from defense waste grouts, the subsequent interactions of the leachate with sediments, and diffusion coefficients for contaminants through asphalt aggregate barriers.

JOHN W. SHADE, Principal Scientist, Grout Technology Section, Westinghouse Hanford Company

B.A.	Geology, Miami University (Ohio)	1960
M.S.	Geology and Chemistry, Miami University (Ohio)	1963
	Geochemistry, University of Michigan	1963-64
Ph.D.	Geochemistry, Pennsylvania State University	1968

Dr. Shade has over 30 years of experience in geochemistry and materials science, with 20 years of experience in nuclear and hazardous waste environmental problems. He has had several years of experience in waste-form development; leach testing methodology development; and studies of waste-form durability, rock-water interactions, waste package systems, in situ vitrification, and cement and glass chemistry. He has provided technical oversight, coordination, and integration for Westinghouse Hanford Company for their support of the Hanford Grout Technology Program. He also wrote Chapter 2 and contributed to other chapters in the areas of grout properties, source term, and engineered system degradation processes.

SANDRA F. SNYDER, Research Scientist, Health Risk Assessment Department, Life Sciences Center, Pacific Northwest Laboratory

B.S.	Environmental Management, Pennsylvania State University	1986
M.S.P.H.	Health Physics, University of North Carolina	1991

Ms. Snyder has been involved in several environmental accumulation and dose assessment projects. She has developed expertise in modeling the environmental dispersion of radioactive materials and parameter selection for these models. Her expertise has been used in this performance assessment to select the appropriate exposure parameters for the scenarios evaluated. She has also contributed to the generation of the dose estimates. She also performed the sensitivity analysis on the dose assessment model.

W. HOWARD SUTHERLAND, Fellow Engineer, Engineering Development Department, Design and Evaluation Section, Westinghouse Hanford Company

B.S.	Chemistry, Brigham Young University	1956
M.S.	Applied Mathematics, Iowa State University	1959
Ph.D.	Engineering Mechanics, University of Washington	In progress

Mr. Sutherland has 34 years of experience in developing and applying nonlinear structural analysis codes to a variety of problems in the aerospace industry, fast reactor core design, and NASA space station program. Mr. Sutherland provided benchmarking/verification of version 2.394gr of PORFLOW, a code used for this performance assessment. He also provided an independent check of all PORFLOW input decks that were used in this performance assessment.

JEFFRY A. VOOGD, Manager, Grout Technology Section, Westinghouse Hanford Company

B.S.	Chemical Engineering, University of Washington	1977
------	--	------

Mr. Voogd is currently manager for technology activities leading to disposal of Hanford's low-level tank waste. His responsibilities in this role include characterization of low-level tank waste, waste form development, engineered system performance testing (vault and barriers), quality verification development, and performance assessment. Prior to this position he was responsible for Hanford's high-level waste form qualification activities, and technical liaison with Savannah River vitrification development testing. His background also includes 5 years of nuclear fuel reprocessing experience.

DALE F. WASHBURN, Technical Writer/Editor, Boeing Computer Services Richland

B.S.	Scientific and Technical Communication University of Washington	1988
------	--	------

Mr. Washburn has 4 years of experience writing and editing safety analyses and regulatory documents related to nuclear processes and hazardous waste disposal. His education includes background in environmental chemistry. He reviewed the performance assessment to ensure continuity among the work of the various contributors and assisted in preparing certain sections.

JOSEPH H. WESTSIK, JR., Senior Research Engineer/Group Leader, Waste Process Engineering Department, Waste Technology Center, Pacific Northwest Laboratory

B.S.	Chemistry, Washington State University	1974
M.S.	Chemical Engineering, University of Washington	1980
M.S.	Engineering Management, Washington State University	1991

Mr. Westsik is the project manager for the Hanford Grout Technology Program, which is charged with preparing this performance assessment. He has worked in the areas of radioactive and hazardous waste management and chemical process engineering. He has been a participant and project manager for several projects to evaluate the performance characteristics of waste forms for the disposal of high-level, transuranic, and low-level radioactive wastes.

GREG A. WHYATT, Senior Development Engineer, Waste Process Engineering Department, Waste Technology Center, Pacific Northwest Laboratory

B.S.	Chemical Engineering, Washington State University	1985
M.S.	Chemical Engineering, Washington State University	1986
	Professional Engineer, State of Washington	

Mr. Whyatt was the manager of the January 1991 version of the grout performance assessment and has acted as a technical contributor and contributing author for this performance assessment. His other involvement in the grout project has included directing pilot-scale grout production to assess the processing characteristics of double-shell slurry feed grout. He has also been involved in testing the liners, asphalt barrier, and other materials to be used in constructing the grout vaults.

BOB V. WINKEL, Westinghouse Hanford Company

B.S.	Civil Engineering, Brigham Young University	1965
M.S.	Structural Engineering, Brigham Young University	1967
Ph.D.	Civil Engineering, University of Colorado	1970

Dr. Winkel has worked for over 23 years as a structural analyst in the nuclear industry, with 19 of those years at Hanford. The majority of his work experience has involved code evaluations (ACI, ASME, AISC) of new and existing structures. Several of these evaluations have involved aging reinforced concrete structures, including B Plant, T Plant, and K Basin. These evaluations have involved aging concerns and structural adequacy of the aging structures for natural phenomena, such as seismic events. He has many years of involvement in professional engineering society activities, and has published several papers. He is currently serving on the ASCE Dynamic Analysis Committee, Structural Capacity and Failure Mode Working Group.

DONALD E. WOOD, Advisory Scientist, Technology Development Department, Westinghouse Hanford Company

B.S.	Physics, University of Nevada	1951
M.S.	Physics, Northwestern University	1953
Ph.D.	Physics, Northwestern University	1956

Dr. Wood is a member of the Steering Committee and a key reviewer for the grout performance assessment. He has 17 years of experience in reliability, safety, and performance assessment activities, and chairs the Performance Assessment Task Team for DOE-HQ.

MARCUS I. WOOD, Principal Scientist, Solid Waste Disposal, Westinghouse Hanford Company

B.S.	Geology, University of North Carolina	1973
Ph.D.	Geology, Brown University	1980

Dr. Wood is currently responsible for developing a performance assessment analysis for the disposal of solid low-level waste in near-surface facilities at the Hanford Site. He has directed numerous projects to quantify the geochemical properties of radionuclides in the Hanford geohydrologic environment.

7.0 References

10 CFR 61. U.S. Nuclear Regulatory Commission. "Licensing Requirements for Land Disposal of Radioactive Waste." *U.S. Code of Federal Regulations*.

10 CFR 100. 1993. U.S. Department of Energy. "Reactor Site Criteria." *U.S. Code of Federal Regulations*.

40 CFR 61. 1992. U.S. Environmental Protection Agency, "National Emission Standard for Hazardous Air Pollutants." *U.S. Code of Federal Regulations*.

40 CFR 141. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations." *U.S. Code of Federal Regulations*.

40 CFR 143. U.S. Environmental Protection Agency. "National Secondary Drinking Water Regulations." *U.S. Code of Federal Regulations*.

40 CFR 191. U.S. Environmental Protection Agency. "Environmental Radiation Protection Standards for Management and Disposal of Spent Nuclear Fuel, High-Level, and Transuranic Radioactive Waste." *U.S. Code of Federal Regulations*.

40 CFR 261. 1992. U.S. Environmental Protection Agency. "Identification and Listing of Hazards." *U.S. Code of Federal Regulations*.

40 CFR 264. 1990. U.S. Environmental Protection Agency, "Standards for Owners and Operators of Hazardous Waste Treatment, Storage, and Disposal Facilities." *U.S. Code of Federal Regulations*.

40 CFR 265. 1990. U.S. Environmental Protection Agency, "Interim Status Standards for Owners and Operators of Hazardous Waste Treatment, Storage, and Disposal Facilities." *U.S. Code of Federal Regulations*.

56 FR 32113. July 15, 1991. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations." *Federal Register*.

56(138) FR 33050. 1991. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations: Radionuclides." Notice of Proposed Rulemaking. *Federal Register*.

56 FR 3597. January 30, 1991. U.S. Environmental Protection Agency, "National Secondary Drinking Water Regulations." *Federal Register*.

56 FR 3578. January 30, 1991. U.S. Environmental Protection Agency, "National Primary Drinking Water Regulations." *Federal Register*.

56 FR 30280. July 1, 1992. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations: Monitoring for Volatile Organic Chemicals; MCLGs and MCLs for Aldicarb Sulfoxide, Aldicarb Sulfone, Pentachlorophenol, and Barium." *Federal Register*.

56 FR 3594. January 30, 1991. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations." *Federal Register*.

56 FR 26460. June 7, 1991. U.S. Environmental Protection Agency. "Maximum Contaminant Level Goals and National Primary Drinking Water Regulations for Lead and Copper." *Federal Register*.

57(138) FR 31776. 1992. "National Primary Drinking Water Regulations - Synthetic Organic Chemicals and Inorganic Chemicals: National Primary Drinking Water Regulations Implementation." *Federal Register*.

57 FR 31838. July 17, 1992. U.S. Environmental Protection Agency. "National Primary Drinking Water Regulations." *Federal Register*.

58 FR 7924. 1992. U.S. Environmental Protection Agency. "Environmental Radiation Protection Standards for the Management and Disposal of Spent Nuclear Fuel, High-Level and Transuranic Radioactive Wastes." Proposed Amendment to 40 CFR 191. *Federal Register*.

Adams, M. R., and N. R. Wing. 1987. *Protective Barrier and Warning Marker System Development Plan*. RHO-RE-PL-35 P, Rockwell Hanford Operations, Richland, Washington.

Advanced Sciences, Inc. *Third-Party Technical Peer Review of Hanford Site Performance Assessment and Grout Performance Assessment*. WHC-SP-0548. Prepared by Advanced Sciences, Inc. for Westinghouse Hanford Company, Richland, Washington.

Albenesius, E. L., and E. L. Wilhite. 1986. *Establishment of New Disposal Capacity for the Savannah River Plant*. DP-MS-86-108, E. I. du Pont de Nemours and Company, Savannah River Laboratory, Aiken, South Carolina.

Amarantos, S., R. DeBatist, K. Broderson, F. P. Glasser, P. E. Pottier, R. Vejmelka, and E. Zamorani. 1985. "Behavior of Intermediate-Waste Forms in Aqueous Environment." In *Radioactive Waste Management and Disposal*. Proceedings of the Second European Community Conference, ed. R. Simon, pp. 252-267. Cambridge University Press, Cambridge, United Kingdom.

American Society for Testing and Materials (ASTM). 1985. "Standard Test Method for Distribution Ratios by the Short-Term Batch Method." In *Annual Book of ASTM Standards*, Vol. 04.08, pp. 766-773, Philadelphia, Pennsylvania.

Ames, L. L., and D. Rai. 1978. *Radionuclide Interactions with Soil and Rock Media*. Rep. EPA 520/6-78-007, Vol. 1, U.S. Environmental Protection Agency, Office of Radiation Programs, Las Vegas, Nevada.

Ames, L. L. and R. J. Seme. 1991. *Compilation of Data to Estimate Groundwater Migration Potential for Constituents in Active Liquid Discharges at the Hanford Site*. PNL-7660, Pacific Northwest Laboratory, Richland, Washington.

ANSI/ASME. 1989. *Quality Assurance Program Standard Requirements for Nuclear Facilities*. ANSI/ASME NQA-1, American National Standards Institute/American Society of Mechanical Engineers, New York.

Bauer, H. H. and J. J. Vaccaro. 1990. *Estimates of Ground Water Recharge to the Columbia Plateau Regional Aquifer System; Washington, Oregon and Idaho for Predevelopment and Current Land Use Conditions*. WRIR 88-4108, U.S. Geological Survey, Tacoma, Washington.

Benson, D. W. 1960. *Review of Soil Chemistry Research at Hanford*. HW-67210, Hanford Atomic Products Operation, Richland, Washington.

Berger, A.L. 1981. "The Astronomical Theory of Paleoclimates." In A. Berger (editor), *Climatic Variations and Variability: Facts and Theories*. D. Reidel Publishing Company, Dordrecht, Holland, pp. 501-525.

Berger, A., J. Imbrie, J. Hays, G. Kukla, and B. Saltzman (editors). 1984. *Milankovich and Climate*. D. Reidel, Dordrecht, Holland.

Berger, A., H. Galle, Th. Fichet, I. Marsiat, and C. Tricot. 1990. "Testing the Astronomical Theory with a Coupled Climate-Ice Sheet Model." *Plaeogeography, Palaeoclimatology, Palaeoecology* (Global and Planetary Change Section) 89:125-141.

Berger, A., H. Gallee, and J. L. Melice. 1991. "The Earth's Future Climate at the Astronomical Time-scale." In G. M. Goodess and J.P. Palutikof, *Future Climate Change and Radioactive Waste Disposal: Proceedings of International Workshop*, NSS/R257, U.K. Nirex Radioactive Waste Disposal, Ltd., Harwell, OX11 ORH, United Kingdom, pp. 148-165.

Bjornstad, B. N. 1984. *Suprabasalt Stratigraphy Within and Adjacent to the Reference Repository Location*. SD-BWI-DP-039, Rockwell Hanford Operations, Richland, Washington.

Blake, G. R. and K. H. Hartge. 1986a. "Particle Density." In *Methods of Soil Analysis, Part 1*. A. Klute, ed. American Society of Agronomy, Madison, Wisconsin, pp. 377-382.

Blake, G. R. and K. H. Hartge. 1986b. "Bulk Density." In *Methods of Soil Analysis, Part 1*. A. Klute, ed. American Society of Agronomy, Madison, Wisconsin, pp. 363-375.

Bouwer, H. and R. C. Rice. 1983. "Effect of Stones on Hydraulic Properties of Vadose Zones." In *Proceedings of the Characterization and Monitoring of the Vadose (Unsaturated) Zone*. National Water Well Association, Worthington, Ohio.

Bredehoeft, J. D. and L. F. Konikow. 1993. "Ground-Water Models: Validate or Invalidate." *Ground Water* 31(2):178-179.

Brockhaus, R. D. 1989. "Preliminary Application of a Fully Three-Dimensional Simulation Model for the Groundwater System at the Hanford Site, Washington." M.S.E. Professional Paper, Environmental Engineering Program, Civil Engineering Department, University of Washington, Seattle.

Browne, E., R. B. Firestone, and V. S. Shirley (ed.). 1986. *Table of Radioactive Isotopes*. John Wiley & Sons, New York.

Calder, N. 1974. "Arithmetic of Ice Ages." *Nature* 252:216-218.

Cary, J. W., G. W. Gee, and G. A. Whyatt. 1991. "Waste Storage in the Vadose Zone Affected by Water Vapor Condensation and Leaching." In *Materials Research Society Symposium Proceedings*, Vol. 212. Materials Research Society, Pittsburgh, Pennsylvania, pp. 871-878.

Case, M. J., R. L. Dodge, T. G. Frangos, W. R. Hansen, W. E. Kennedy, Jr., D. W. Layton, D. W. Lee, and E. L. Wilhite. 1989. *Recommended Format and Content for DOE-Low-Level Waste Disposal Facility Radiological Performance Assessment Reports*. DOE/LLW-81, U.S. Department of Energy, Washington, D.C.

Chatters, J. C. 1991. "Long-Term Climate Change Effects," L. L. Cadwell (editor). *Hanford Site Protective Barrier Development Program: Fiscal Year 1990 Highlights*. PNL-7831, Pacific Northwest Laboratory, Richland, Washington, pp. 2.23-3.1.

Chatters, J. C. and K. A. Hoover. 1992. "Response of the Columbia River Fluvial System to Holocene Climatic Change." *Quaternary Research*. Vol. 37, pp. 42-59.

Clemmer, R. G., R. P. Allen, and L. K. Fetrow. 1992. *Hydrogen Permeation of Asphalt Test Results - FY-1992*. Hanford Grout Technology Program, HGTP-92-0605-02, Pacific Northwest Laboratory, Richland, Washington.

Connelly, M. P., B. H. Ford, and J. V. Borghese. 1992a. *Hydrogeologic Model for the 200 West Groundwater Aggregate Area*. WHC-SD-EN-TI-014, Westinghouse Hanford Company, Richland, Washington.

- Connelly, M. P., B. H. Ford, J. V. Borghese, S. Trent, and J. Lindberg. 1992b. *Hydrogeologic Model for the 200 East Groundwater Aggregate Area*. WHC-SD-EN-TI-019, Westinghouse Hanford Company, Richland, Washington.
- Crank, J. 1975. *The Mathematics of Diffusion*. Oxford University Press, New York.
- Cropper, J. P. and H. C. Fritts. 1986. *A 360 Year Temperature and Precipitation Record for the Pasco Basin Derived from Tree Rings*. DOE-RL-01830-T46, U.S. Department of Energy, Richland, Washington.
- Crowley, T. J. and G. R. North. 1991. *Paleoclimatology*. Oxford Monographs on Geology and Geophysics No. 16, Oxford University Press, New York.
- Cushing, C. E., editor. 1991. *Hanford Site National Environmental Policy Act (NEPA) Characterization*. PNL-6415, Rev. 4. Pacific Northwest Laboratory, Richland, Washington.
- Daiev Ch. T., and G. P. Vassilev. 1985. "On the Diffusion of ^{90}Sr from Radioactive Wastes Bitumenized by the Mould Method." *Journal of Nuclear Materials* 127, pp. 132-136, North Holland, Amsterdam.
- Dames and Moore. 1988. *Geotechnical and Corrosion Investigation, Grout Vaults, Hanford, Washington*. October 10, 1988. Report for Kaiser Engineers, Inc., by Dames and Moore, Seattle, Washington, Contract No. 10805-282-016.
- Dayal, R., D. C. Schweitzer, and R. E. Davis. 1984. "Wet and Dry Cycle Leaching: Aspects of Research in the Unsaturated Zone." In *NRC Nuclear Waste Geochemistry '83*, eds. D. H. Alexander and G. F. Birchard, pp. 440-453. NUREG/CP-0052, U.S. Nuclear Regulatory Commission, Washington, D.C.
- Delaney, C. N., K. A. Lindsey, and S. P. Reidel. 1991. *Geology and Hydrology of the Hanford Site: A Standardized Text for Use in WHC Documents and Reports*. WHC-SD-ER-TI-003, Rev. 0. Westinghouse Hanford Company, Richland, Washington.
- Delegard, C. H., and G. S. Barney. 1983. *Effects of Hanford High-Level Waste Components on Sorption of Cobalt, Strontium, Neptunium, Plutonium, and Americium of Hanford Sediments*. RHO-RE-ST-1 P, Rockwell Hanford Operations, Richland, Washington.
- Dodge, R. L., W. R. Hansen, W. E. Kennedy, Jr., D. W. Layton, D. W. Lee, S. T. Maheras, S. M. Neuder, E. L. Wilhite, R. U. Curl, K. F. Grahn, B. A. Heath, and K. H. Turner. 1991. *Performance Assessment Review Guide for DOE Low-Level Radioactive Waste Disposal Facilities*. DOE/LLW-93. Prepared by Dames and Moore, Denver, Colorado, for the U.S. Department of Energy, Office of Environmental Restoration and Waste Management. DOE Field Office, Idaho Falls, Idaho.

- Dougherty, D. R., R. F. Pietrzak, M. Fuhrmann, and P. Colombo. 1986. *Accelerated Leach Test Program: Annual Report*. BNL-52042, Brookhaven National Laboratory, Upton, New York.
- Dunning, D. E., Jr. and G. Schwarz. 1981. "Variability of Human Thyroid Characteristics and Estimates of Dose from Ingested I-131." *Health Physics* 40:661-675.
- ERDA (Energy Research and Development Administration). 1975. *Final Environmental Statement Waste Management Operations, Hanford Reservation*, Richland, Washington. ERDA 1538, Vol. 1-2. U.S. Energy Research and Development Administration, Washington, D.C.
- Fecht, K. R., S. P. Reidel, and A. M. Tallman. 1987. "Paleodrainage of the Columbia River System on the Columbia Plateau of Washington State--A Summary." *Selected Papers on the Geology of Washington*, Division of Geology and Earth Resources, Bulletin 77, p. 219-248, edited by J.E. Schuster.
- Fitzgerald, C. L., H. W. Godbee, R. E. Blanco, and W. Davis, Jr. 1970. "The Feasibility of Incorporating Radioactive Wastes in Asphalt or Polyethylene." *Nuclear Applications and Technology* 9:821.
- Freeze, R. A. and J. A. Cherry. 1979. *Groundwater*. Prentice-Hall, Inc., Englewood Cliffs, New Jersey.
- Fuhrmann, M., R. F. Pietrzak, E. M. Franz, J. H. Heiser, and P. Colombo. 1989. *Optimization of the Factors that Accelerate Leaching*. BNL-52204, Brookhaven National Laboratory, Upton, New York.
- Gee, G. W., A. C. Campbell, P. J. Wierenga, and T. L. Jones. 1981. *Unsaturated Moisture and Radionuclide Transport: Laboratory Analysis and Modeling*. PNL-3616, Pacific Northwest Laboratory, Richland, Washington.
- Gee, G. W. and J. W. Bauder. 1986. "Particle-Size Analysis." In *Methods of Soil Analysis, Part 1*. A. Klute, ed. American Society of Agronomy, Madison, Wisconsin, pp. 383-409.
- Gee, G. W., M. J. Fayer, M. L. Rockhold, and M. D. Campbell. 1992. "Variations in Recharge at the Hanford Site." *Northwest Science* 66(4):237-250.
- Graham, M. J., M. D. Hall, S. R. Strait, and W. R. Brown. 1981. *Hydrology of the Separations Area*. RHO-ST-42, Rockwell Hanford Operations, Richland, Washington.
- Gramlich, L. H. 1987. "Precipitation Variation in the Pacific Northwest (1675-1975) as Reconstructed from Tree Rings." *Annals of the Association of American Geographers* 77:19-29.
- Grazulis, T.P. 1984. *Violent Tornado Climatology, 1880-1982*. NUREG/CR-3670, U.S. Nuclear Regulatory Commission, Washington, D.C.
- Grim, R. E. 1968. *Clay Mineralogy*. McGraw-Hill Book Company, New York.

Gruhlke, J. M., F. L. Galpin, and W. F. Holcomb. 1989. "Overview of EPA's Environmental Standards for the Land Disposal of LLW and NARM Waste--1989." In *Eleventh Annual Department of Energy Low-Level Waste Management Conference*, Vol. I, pp. RU24-RU32. CONF-890854. September 22-24, 1989, Pittsburgh, Pennsylvania. Idaho National Engineering Laboratory, Idaho Falls, Idaho.

Hajek, B. F. 1966. *Plutonium and Americium Mobility in Soils*. BNWL-CC-925, Pacific Northwest Laboratory, Richland, Washington.

Hanford Future Site Uses Working Group. 1992. *The Future for Hanford: Uses and Cleanup*. Final Report of the Hanford Future Site Uses Working Group.

Hanks, R. J. and G. L. Ashcroft. 1980. *Applied Soil Physics; Soil Water and Temperature Applications*. Springer-Verlag, New York, pp. 91-97.

Hansen, J., D. Johnson, A. Lacis, S. Lebedeff, P. Lee, D. Rind, and G. Russell. 1981. "Climate Impact of Increasing Atmospheric Carbon Dioxide." *Science*, Vol. 213, pp. 957-966.

Harr, M. E. 1962. *Groundwater and Seepage*. McGraw-Hill Book Company, New York.

Harris, A. W., A. Atkinson, and P. A. Claisse. 1992. "Transport of Gases in Concrete Barriers." *Waste Management* 12:155-178.

Hartley, J. N., J. A. Glissmeyer, and O. F. Hill. 1985. *Methods for Estimating Radioactive and Toxic Airborne Source Terms for Uranium Milling Operations*. NUREG/CR-4088, PNL-5338. Prepared by Pacific Northwest Laboratory for the U.S. Nuclear Regulatory Commission, Washington, D.C.

Hays, J. D., J. Imbrie, N. J. Shackleton. 1976. "Variations in the Earth's Orbit: Pacemakers of the Ice Ages." *Science*, 194:1121-1132.

Hendrickson, D. W. 1993. Engineering Change Notice 163849 to WHC-SD-WM-TI-528, *Grout Treatment Facility Waste Feed Projections*. Westinghouse Hanford Company, Richland, Washington.

Hendrickson, D. W. and J. M. Conner. 1993. *Grout Treatment Facility Waste Feed Projections*. WHC-SD-WM-TI-528, Rev. 0. Westinghouse Hanford Company, Richland, Washington.

Hillel, D. 1982. *Introduction to Soil Physics*. Academic Press, Inc., New York.

Hills, R. G. and P. J. Wierenga. 1991. *Model Validation at the Las Cruces Trench Site*. NUREG/CR-5716, U.S. Nuclear Regulatory Commission, Washington, D.C.

Höglund, S., L. Eliasson, B. Allard, K. Andersson and B. Torstenfelt. 1985. "Sorption of Some Fission Products and Actinides in Concrete Systems." *Scientific Basis for Nuclear Waste Management IX*. 50:683-690, Materials Research Society, Pittsburgh, Pennsylvania.

Houghton, J. T., G. J. Jenkins, and J. J. Ephraums. 1990. *Climate Change: The IPCC Scientific Assessment*. Cambridge University Press, Cambridge, United Kingdom.

Huang, F. H., D. E. Mitchell, and J. M. Conner. 1993. *Quality Verification Report of Phosphate/Sulfate Waste Grout*. WHC-SD-WM-RPT-066, Westinghouse Hanford Company, Richland, Washington.

ICRP (International Commission on Radiological Protection). 1975. "Report of the Task Group on Reference Man." *ICRP Publication 23*, Pergamon Press, Oxford, United Kingdom.

ICRP. 1977. "Recommendations of the International Commission on Radiological Protection." *ICRP Publication 26, Annals of the ICRP*, 2, No. 3.

ICRP. 1979. "Limits for Intakes of Radionuclides by Workers." *ICRP Publication 30, Part 1* (1979) *Annals of the ICRP*, 2, No. 3/4:1-62. Supplement to Part 1 (1979) *Annals of the ICRP*, 3:84, 202, 236, 414, 456. Supplement to Part 2 (1981) *Annals of the ICRP*, 5:195. Supplement A to Part 3 (1982) *Annals of the ICRP*, 7:17.

ICRP. 1979-1988. *Limits for Intakes of Radionuclides by Workers*. ICRP Publication 30, Parts 1-4 (and supplements), Vol. 2 (No. 3/4), Vol. 4 (No. 3/4), Vol. 6 (No. 2/3), Vol. 8 (No. 4), and Vol. 19 (No. 4), Pergamon Press. Elmsford, New York.

ICRP. 1986. *The Metabolism of Plutonium and Related Elements*. ICRP Publication 48, Pergamon Press, New York.

ICRP. 1991. *1990 Recommendations of the International Commission on Radiological Protection*. ICRP Publication 60, Pergamon Press, Oxford, United Kingdom.

Imbrie, J., and J. Z. Imbrie. 1980. "Modeling the Climatic Response to Orbital Variations." *Science* 207:943-953.

Jacobson, E. A. and M. D. Freshley. 1990. *An Initial Inverse Calibration of the Ground-Water Flow Model for the Hanford Unconfined Aquifer*. PNL-7144, Pacific Northwest Laboratory, Richland, Washington.

Johnson, V. G. 1993. *Groundwater Status Report*. WHC-EP-0595, Westinghouse Hanford Company, Richland, Washington.

- Kaiser Engineers Hanford Company. 1989. "Construction Specifications for the Diffusion Break." Specification #B-714-C2, Rev. 1, Section 02147, pages 02147-1 through 02147-10. Kaiser Engineers Hanford Company, Richland, Washington.
- Kasza, G. L., S. F. Harris, and M. J. Hartman. 1990. *Ground Water Maps of the Hanford Site, December 1990*. WHC-EP-0394-1, Westinghouse Hanford Company, Richland, Washington.
- Kennedy, W. E., Jr. and D. L. Streng. 1992. *Residual Radioactive Contamination from Decommissioning: Volume 1, Technical Basis for Translating Contamination Levels to Annual Effective Dose Equivalent*. NUREG/CR-5512, Pacific Northwest Laboratory, Richland, Washington.
- Kemper, W. D., and J. C. van Schaik. 1966. "Diffusion of Salts in Clay-Water Systems." *Soil Sci. Am. Proc.* 30:534-540.
- Kline, N. W., A. K. Runchal, and R. G. Baca. 1983. *PORFLO Computer Code: Users Guide*. RHO-BW-CR-138P, Rockwell Hanford Operations, Richland, Washington.
- Klute, A. and C. Dirksen. 1986. "Hydraulic Conductivity and Diffusivity: Laboratory Methods." In *Methods of Soil Analysis, Part 1*. A. Klute, ed. American Society of Agronomy, Madison, Wisconsin. pp. 687-732.
- Knoll, K. C. 1966. *Reaction of High-Salt Aqueous Plus Organic Waste with Soil*. Technical Report No. BNWL-CC-313, Pacific Northwest Laboratory, Richland, Washington.
- Knoll, K. C. 1969. *Reaction of Organic Wastes in Soil*. Technical Report No. BNWL-860, Pacific Northwest Laboratory, Richland, Washington.
- Kocher, D. C., R. W. Leggett, D. E. Dunning, Jr., M. T. Ryan, and K. F. Eckerman. 1980. *Uncertainties in the Calculation of Long-Term Collective Dose and Health Effects--A Preliminary Assessment*. NUREG/CR-1303, ORNL/NUREG/TM-378. Oak Ridge National Laboratory, Oak Ridge, Tennessee.
- Kramer, S. L. and R. D. Holtz. August 1989. *Experimental Investigation of Seismically-Induced Particle Migration*. Department of Civil Engineering, University of Washington, Seattle, Washington.
- Kukla, G. J. 1981. "Pleistocene Climates on Land," A. Berger (editor). *Climate Variations and Variability: Facts and Theories*. D. Reidel Publishing Company, Dordrecht, Holland, pp. 207-232.
- Kukla, G., A. Berger, R. Lotti, and J. P. Brown. 1981. "Orbital Signature of Interglacials." *Nature* 290:295-300.
- Lea, F. M. 1971. *The Chemistry of Cement and Concrete*. Chemical Publishing Company, Inc. p. 727.

Lindberg, J. W., J. V. Borghese, B. N. Bjornstad, and M. P. Connelly. 1993. *Geology and Aquifer Characteristics of the Grout Treatment Facility*. WHC-SD-EN-TI-071, Rev. 0. Westinghouse Hanford Company, Richland, Washington.

Lindsay, W. L. 1979. *Chemical Equilibria in Soils*. Wiley Interscience, New York.

Lindsey, K. A. 1991. *Revised Stratigraphy for the Ringold Formation, Hanford Site, South-central Washington*. WHC-SD-EN-EE-004, Rev. 0, Westinghouse Hanford Company, Richland, Washington.

Lindsey, K. A. and D. R. Gaylord. 1989. *Sedimentology and Stratigraphy of the Miocene-Pliocene Ringold Formation, Hanford Site, South-Central Washington*. WHC-SA-0740-FP, Westinghouse Hanford Company, Richland, Washington.

Lindsey, K. A., B. N. Bjornstad, and M. P. Connelly. 1991. *Geologic Setting of the 200 West Area: An Update*. WHC-SD-EN-TI-008, Westinghouse Hanford Company, Richland, Washington.

Lindsey, K. A., B. N. Bjornstad, J. W. Lindberg, and K. M. Hoffmann. 1992. *Geologic Setting of the 200 East Area: An Update*. WHC-SD-EN-TI-012, Westinghouse Hanford Company, Richland, Washington.

Lindsey, K. A. 1992. *Geology of the Northern Part of the Hanford Site: An Outline of Data Sources and the Geologic Setting of the 100 Areas*. WHC-SD-EN-TI-011. Westinghouse Hanford Company, Richland, Washington.

Lokken, R. O. 1992. *Formulation Verification Study Results for Tank 106-AN Waste*. PNL-7966, Pacific Northwest Laboratory, Richland, Washington.

Lokken, R. O., P.F.C. Martin, and J. W. Shade. 1992. *Durability of Double-Shell Tank Waste Grouts*. PNL-7835, Pacific Northwest Laboratory, Richland, Washington.

Lokken, R. O., L. M. Bagaasen, P.F.C. Martin, S. E. Palmer, and C. M. Anderson. 1993. *Characterization Results for 106-AN Grout Produced in a Pilot-Scale Test*. PNL-8655, Pacific Northwest Laboratory, Richland, Washington.

Luey, J. and S. W. Li. 1993. *Determination of the Biodegradation Rate of Asphalt for the Hanford Grout Vaults*. PNL-8599, Pacific Northwest Laboratory, Richland, Washington.

Marun, P.F.C. and R. O. Lokken. 1992. *Characterization of a Low-Level Radioactive Waste Grout: Sampling and Test Results*. PNL-8067, Pacific Northwest Laboratory, Richland, Washington.

Melice, J. L., and A. Berger. 1989. *Modele de prevision statistique du type Box-Jenkins pour la prevision du climat des 10.000 prochaines annees*. Scientific Report 1989/6, Institut d'Astronomie et de Geophysique G. Lemaitre, Universite Catholique de Louvain-la-Neuve, Belgium.

- Merck Index. 1983. *The Merck Index*, ed. M. Windholz. 10th ed. Merck & Co., Rahway, New Jersey.
- Mualem, Y. 1976. "A New Model for Predicting the Hydraulic Conductivity of Unsaturated Porous Media." *Water Resources Research*, 12(3):513-522.
- Muller, A. B., D. Langmuir, and L. E. Duda. 1983. "The Formulation of an Integrated Physiochemical-Hydrologic Model for Predicting Waste Nuclide Retardation in Geologic Media." In *Scientific Basis for Nuclear Waste Management VI*, ed. D. G. Brookins, Vol. 15, pp. 547-564. Elsevier Science Publishing Company, New York.
- Muurinen, A., J. Rantanen, R. Ovaskainen, and O. J. Heinonen. 1983. "Diffusion Measurements in Concrete and Compacted Bentonite." In *Scientific Basis for Nuclear Waste Management VI*, ed. D. G. Brookins, Vol. 15, pp. 777-784. Elsevier Science Publishing Company, New York.
- Myers, C. W., S. M. Price, J. A. Caggiano, M. P. Cochran, W. J. Czimer, N. J. Davidson, R. C. Edwards, K. R. Fecht, G. E. Holmes, M. G. Jones, J. R. Kunk, R. D. Landon, R. K. Ledgerwood, J. T. Lillie, P. E. Long, T. H. Mitchell, E. H. Price, S. P. Reidel, and A. M. Tallman. 1979. *Geologic Studies of the Columbia Plateau: A Status Report*. RHO-BWI-ST-4, Rockwell Hanford Operations, Richland, Washington.
- Myers, C. W. and S. M. Price. 1981. "Bedrock Structure of the Cold Creek Syncline Area." In *Subsurface Geology of the Cold Creek Syncline*. RHO-BWI-ST-14, Rockwell Hanford Operations, Richland, Washington.
- Napier, B. A., R. A. Peloquin, D. L. Streng, and J. V. Ramsdell. 1988. *Hanford Environmental Dosimetry Upgrade Project. GENII - The Hanford Environmental Radiation Dosimetry Software System*. PNL-6584, Vol. 1-3, Pacific Northwest Laboratory, Richland, Washington.
- National Council on Radiation Protection and Measurements (NCRP). 1984. *Radiological Assessment: Predicting the Transport, Bioaccumulation, and Uptake by Man of Radionuclides Released to the Environment*. NCRP Report No. 76, National Council on Radiation Protection, Bethesda, Maryland.
- NCRP. 1987. *Ionizing Radiation Exposure of the Population of the United States*. Report No. 93, National Council on Radiation Protection, Bethesda, Maryland.
- Newcomb, R. C. 1958. "Ringold Formation of the Pleistocene Age in the Type Locality, the White Bluffs, Washington." *American Journal of Science* 33(1):328-340.
- Newcomb, R. C., J. R. Strand, and F. J. Frank. 1972. *Geology and Groundwater Characteristics of the Hanford Reservation of the U.S. Atomic Energy Commission, Washington*. Geological Survey Professional Paper 717, U.S. Geological Survey, Washington, D.C.

- Olsen, S. R., and W. D. Kemper. 1968. *Advances in Agronomy* 20:91-151.
- Olsen, S. R., W. D. Kemper, and J. C. van Schaik. 1965. "Self-Diffusion Coefficients of Phosphorus in Soil Measured by Transient and Steady-State Methods." *Soil Sci. Am. Proc.* 29:154-158.
- Petersen, E. L. and S. E. Larsen. 1978. "A Statistical Study of a Composite Isotopic Paleotemperature Series from the Last 700,000 Years." *Tellus* 30:193-200.
- Piepho, M. G. 1994. *Grout Performance Assessment Results of Benchmark, Base, Sensitivity, and Degradation Cases*. WHC-SD-WM-TI-561, Westinghouse Hanford Company, Richland, Washington.
- Piepho, M. G., W. H. Sutherland, P. D. Rittmann, and F. W. Mann. 1994. *The Grout Performance Assessment Code System (GPACS) with Verification and Benchmarking*. WHC-SD-WM-UM-019, Westinghouse Hanford Company, Richland, Washington.
- Porter, L. K., W. D. Kemper, R. D. Jackson, and B. C. Stewart. 1960. "Chloride Diffusion in Soils as Influenced by Moisture Content." *Soil Sci. Soc. Am. Proc.* 24:460-463.
- PSPL. 1982. *Skagit/Hanford Nuclear Project, Preliminary Safety Analysis Report*. Vol. 4, App. 20, Amendment 23, Puget Sound Power and Light Company, Bellevue, Washington.
- Reynolds, K. D. 1992. *Generic Well Specification Groundwater Monitoring Wells*. WHC-SD-014, Rev. 7. Westinghouse Hanford Company, Richland, Washington.
- Reidel, S. P. and P. R. Hooper, editors. 1989. "Volcanism and Tectonism in the Columbia River Flood-Basalt Province." Special Paper 239, Geological Society of America, Boulder, Colorado, p. 386, plate 1.
- Richards, L. A. 1931. "Capillary Conduction of Liquids Through Porous Mediums." *Physics* 1:318-333.
- Riebling, E. F. and J. G. Fadeff. 1991. *Grout Formulation Standard Criteria Document*. WHC-SD-WM-CSD-003, Rev. 0. Westinghouse Hanford Company, Richland, Washington.
- Rockhold, M. L., M. J. Fayer, and P. R. Heller. 1993. *Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford*. PNL-8813, Pacific Northwest Laboratory, Richland, Washington.
- Routson, R. C., G. S. Barney, and R. O. Seil. 1978. *Measurement of Fission Product Sorption Parameters for Hanford 200 Area Sediment Types: Progress Report*. RHO-LD-73, Rockwell Hanford Operations, Richland, Washington.

- Routson, R. C., G. S. Barney, and R. M. Smith. 1980. *Hanford Site Sorption Studies for the Control of Radioactive Wastes: A Review*. RHO-SA-155, Rev. 1, Rockwell Hanford Operations, Richland, Washington.
- Routson, R. C., G. S. Barney, R. H. Smith, C. H. Delegard, and L. Jensen. 1981. *Fission Product Sorption Parameters for Hanford 200 Area Sediment Types*. RHO-ST-35, Rockwell Hanford Operations, Richland, Washington.
- Routson, R. C., G. Jansen, and A. V. Robinson. 1976. "²⁴¹Am, ²³⁷Np, and ⁹⁹Tc Sorption on Two United States Subsoils from Differing Weathering Intensity Areas." *Health Physics* 33:311-317.
- Routson, R. C., and R. J. Serne. 1972. *One-Dimensional Model of the Movement of Trace Radioactive Solute Through Soil Columns: The PERCOL Model*. BNWL-1718, Pacific Northwest Laboratory, Richland, Washington.
- Routson, R. C. and V. G. Johnson. 1990. "Recharge Estimates for the Hanford Site 200 Area Plateau." *Northwest Science* 64:150-158.
- Runchal, A. K. and B. Sagar. 1989. *PORFLO-3: A Mathematical Model for Fluid Flow, Heat, and Mass Transport in Variably Saturated Geologic Media, Users Manual, Version 1.0*. WHC-EP-0041, Westinghouse Hanford Company, Richland, Washington.
- Runchal, A. K. and B. Sagar. 1992. *PORFLOW: A Model for Fluid Flow, Heat, and Mass Transport in Multifluid, Multiphase Fractured or Porous Media, User Manual, Version 2.4*. ACRi/016/Rev. G., Analytic and Computational Research, Inc., Los Angeles, California.
- Runchal, A. K., B. Sagar, R. G. Baca, and N. W. Kline. 1985. *PORFLO - A Continuum Model for Fluid Flow, Heat Transfer, and Mass Transport in Porous Media*. RHO-BW-CR-150P, Rockwell Hanford Operations, Richland, Washington.
- Sagar, B. and A. K. Runchal. 1990. *PORFLO-3; A Mathematical Model for Fluid Flow, Heat, and Mass Transport in Variably Saturated Geologic Media, Theory and Numerical Methods, Version 1.0*. WHC-EP-0042, Westinghouse Hanford Company, Richland, Washington.
- Sambell, R.A.J., C. Smitton, and A. Elsdon. 1982. "A Contribution Towards a Standard Leach Test on Immobilized Low and Medium Level Waste." *Nucl. Chem. Waste Manage.* 3:125-129.
- Schneider, S. H. 1989. *Global Warming*. Sierra Club Books, San Francisco, California.
- Serkowski, J. A. and W. A. Jordan. 1989. *Operational Groundwater Monitoring at the Hanford Site - 1988*. WHC-EP-0260, Westinghouse Hanford Company, Richland, Washington.

Seme, R. J. 1990. "Grouted Waste Leach Tests: Pursuit of Mechanisms and Data for Long-Term Performance Assessment." *Scientific Basis for Nuclear Waste Management XIII*, eds. V. M. Oversby, and P. W. Brown, Vol. 176, pp. 91-99. Materials Research Society, Boston.

Seme, R. J. and M. I. Wood. 1990. *Hanford Waste-Form Release and Sediment Interaction*. PNL-7297, Pacific Northwest Laboratory, Richland, Washington.

Seme, R. J., W. J. Martin, S. B. McLaurine, S. P. Airhart, V. L. LeGore, and R. L. Treat. 1987. *Laboratory Leach Tests of Phosphate/Sulfate Waste Grout and Leachate Adsorption Tests Using Hanford Sediment*. PNL-6019, Pacific Northwest Laboratory, Richland, Washington.

Seme, R. J., W. J. Martin, R. O. Lokken, V. L. LeGore, C. W. Lindenmier, P. F. C. Martin. 1989. *Leach and EP Toxicity Tests on Grouted Waste from Tank 106-AN*. PNL-6960, Pacific Northwest Laboratory, Richland, Washington.

Seme, R. J., R. O. Lokken, and L. J. Criscenti. 1992. "Characterization of Grouted Low-Level Waste to Support Performance Assessment." In *Waste Management*, Vol. 12, Pergamon Press, Elmsford, New York, pp. 271-287.

Seme, R. J., C. W. Lindenmeier, J. L. Conca, J. A. Campbell, V. L. LeGore, J. E. Amonette, K. J. Cantrell, and M. I. Wood. 1993. *Solid-Waste Leach Characteristics and Contaminant-Sediment Interactions. Volume I: Batch Leach and Adsorption Tests and Sediment Characterization*. PNL-8889, Vol. 1. Pacific Northwest Laboratory, Richland, Washington.

Seme, R. J., and D. Rai. 1976. "Adsorption-Precipitation Behavior of Eu in Soils and Standard Clays." *Agronomy Abstracts*, p. 132.

Seme, R. J., R. C. Routson, and D. A. Cochran. 1973. *Experimental Methods for Obtaining PERCOL Model Input Verification Data*. BNWL-1721, Pacific Northwest Laboratory, Richland, Washington.

Sewart, G. H., W. T. Farris, D. G. Huizenga, A. H. McMakin, G. P. Streile, and R. L. Treat. 1987. *Long-Term Performance Assessment of Grouted Phosphate/Sulfate Waste From N Reactor Operations*. PNL-6152, Pacific Northwest Laboratory, Richland, Washington.

Sheppard, J. C., J. A. Kittrick, and T. L. Hardt. 1976. *Determination of Distribution Ratios and Diffusion Coefficients of Neptunium, Americium, and Curium in Soil-Aquatic Environments*. RLO-2221-T-12-2 (WSU 76/13/33), Washington State University, Pullman, Washington.

Smith, R. M. and W. R. Gorst. 1990. *RCRA Ground-Water Monitoring Projects for Hanford Facilities: Annual Progress Report for 1989*. PNL-7215, Pacific Northwest Laboratory, Richland, Washington.

- Smoot, J. L., J. E. Szecsody, B. Sagar, G. W. Gee, and C. T. Kincaid. 1989. *Simulations of Infiltration of Meteoric Water and Contaminant Plume Movement in the Vadose Zone at Single-Shell Tank 241-T-106 at the Hanford Site*. WHC-EP-0332, Westinghouse Hanford Company, Richland, Washington.
- Stone, W. A., J. M. Thorp, O. P. Gifford, and D. J. Hoitink. 1983. *Climatological Summary for the Hanford Area*. PNL-4622, Pacific Northwest Laboratory, Richland, Washington.
- Strack, O.D.L. 1989. *Groundwater Mechanics*. Prentice-Hall, Englewood Cliffs, New Jersey.
- Standard Design Criteria (SDC)-4.1. September 6, 1989. *Standard Arch.-Civil Design Criteria, Design Loads for Facilities*. SDC-4.1, Rev. 11, Westinghouse Hanford Company, Richland, Washington.
- Sudicky, E. A. 1986. "A Natural Gradient Experiment on Solute Transport in a Sand Aquifer: Spatial Variability and Its Role in the Dispersion Process." *Water Resour. Res.* 22:2069-2082.
- Swanson, L. C., D. C. Weekes, S. P. Luttrell, R. M. Mitchell, D. S. Landeen, A. R. Johnson, and R. C. Roos. 1988. *Grout Treatment Facility Environmental Baseline and Site Characterization Report*. WHC-EP-0150, Westinghouse Hanford Company, Richland, Washington.
- Tallent, O. K., E. W. McDaniel, G. D. Del Cul, K. E. Dodson, and D. R. Trotter. 1988. "Immobilization of Technetium and Nitrate in Cement-Based Materials." *Mat. Res. Soc. Symp. Proc.* 12:23-32.
- Tallman, A. M., J. T. Lillie, K. R. Fecht, C. W. Myers, and S. M. Price. 1981. "Suprabasalt Sediments of the Cold Creek Syncline Area." *Subsurface Geology of the Cold Creek Syncline*. RHO-BWI-ST-14, Rockwell Hanford Operations, Richland, Washington.
- U.S. Bureau of the Census. 1977. *1974 Census of Agriculture*. Volume 1(47), Washington State and County Data. U.S. Department of Commerce, Washington, D.C.
- U.S. Department of Commerce. 1991. *1990 U.S. Census of Population and Housing, State and County Profiles, Washington* (Summary Tape File 1A for Washington State). Office of Financial Management, U.S. Department of Commerce, Washington, D.C.
- U.S. Department of Energy (DOE). 1986a. *Environmental Assessment for the Grouting and Near-Surface Disposal of Phosphate/Sulfate Hanford Facilities Waste*. DOE/EA-0312, U.S. Department of Energy, Washington, D.C.
- U.S. DOE 1986b. "Safety of Nuclear Facilities." DOE Order 5480.5.
- U.S. DOE. 1987. *Final Environmental Impact Statement: Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes*. DOE/EIS-0113, Vol. 1-5, U.S. Department of Energy, Washington, D.C.

U.S. DOE. 1988a. "Radioactive Waste Management." DOE Order 5820.2A.

U.S. DOE. 1988b. "General Environmental Protection Program." DOE Order 5400.1.

U.S. DOE. 1988c. *Consultation Draft Site Characterization Plan*. DOE/RW-0164, Vols. 1-9, Office of Civilian Radioactive Waste Management, U.S. Department of Energy, Washington, D.C.

U.S. DOE. 1990a. "Radiation Protection of the Public and the Environment." DOE Order 5400.5.

U.S. DOE. 1990b. *Grout Treatment Facility Dangerous Waste Permit Application, Rev. 1*. DOE-RL 88-27, U.S. Department of Energy, Richland, Washington.

U.S. DOE. 1992. "Nuclear Safety Analysis Reports." DOE Order 5480.23.

U.S. DOE-RL. 1990. "Radioactive Waste Management." Richland Operations Supplement to DOE-Order 5820.2A.

U.S. DOE-RL. 1992a. *Grout Treatment Facility Dangerous Waste Permit Application, Rev. 2*. U.S. Department of Energy - Richland Field Office, Richland, Washington.

U.S. DOE-RL. 1992b. *Annual Report for RCRA Groundwater Monitoring Projects at Hanford Site Facilities for 1991 - Progress Report*. DOE/RL-92-03, U.S. Department of Energy, Richland Operations, Richland, Washington.

U.S. DOE-RL. 1993a. *Phase I Remedial Investigation Report for 200-BP-1 Operable Unit*. DOE/RL-92-70, U.S. Department of Energy, Richland Operations, Richland, Washington.

U.S. DOE-RL. 1993b. *200 East Groundwater Aggregate Area Management Study Report*. DOE/RL-92-19, U.S. Department of Energy, Richland Operations, Richland, Washington.

U.S. EPA. 1986. *Test Methods for Evaluating Solid Waste*. EPA/SW-846, Office of Solid Waste and Emergency Response, Washington, D.C. Available from the National Technical Information Service, Springfield, Virginia.

USGS (U.S. Geological Survey). 1987. *Subsurface Transport of Radionuclides in Shallow Deposits of the Hanford Nuclear Reservation, Washington--Review of Selected Previous Work and Suggestions for Further Study*. U.S. Geological Survey Open-File Report 87-222, U.S. Geologic Survey, Denver, Colorado.

U.S. Nuclear Regulatory Commission (NRC). 1978. *Safety Evaluation Report Related to Operation of Fast Flux Test Facility, U.S. Department of Energy*. NUREG-0358, Office of Nuclear Reactor Regulation, U.S. Nuclear Regulatory Commission, Washington, D.C.

U.S. NRC. 1982. *Safety Evaluation Report Related to the Operation of WPPSS Nuclear Project No. 2*. NUREG-0892, Supplement No. 1, U.S. Nuclear Regulatory Commission, Washington, D.C.

van Genuchten, M. Th. 1978. *Calculating the Unsaturated Hydraulic Conductivity with a New Closed-Form Analytical Model*. Technical Report No. 78-WR-08. Water Resources Program, Department of Civil Engineering, Princeton University, Princeton, New Jersey.

van Genuchten. 1980. "A Closed Form Equation for Predicting the Hydraulic Conductivity of Unsaturated Soils." *Soil Sci. Soc. of Am. J.* 44:892-898.

Vanselow, L. D. 1989. *Functional Design Criteria Transportable Grout Facility Project B-475*. SD-475-FDC-001, Rev. 5. Westinghouse Hanford Company, Richland, Washington.

Walker, F. W., J. R. Parrington, and F. Feiner. 1989. *Nuclides and Isotopes; 14th Edition*. General Electric Company, San Jose, California.

Walters, W. H., R. L. Dirkes, and B. A. Napier. 1992. *Literature and Data Review for the Surface-Water Pathway: Columbia River and Adjacent Coastal Areas*. PNWD-2034/HEDR, Battelle, Pacific Northwest Laboratories, Richland, Washington.

WAC (Washington Administrative Code). 1989. "Dangerous Waste Regulations," WAC 173-303. Washington State Department of Ecology, Olympia, Washington.

WAC. 1992. Washington State Department of Social and Health Services, "Public Water Supplies." WAC 246-290, Olympia, Washington.

Watson, E. C., C. D. Becker, R. E. Fitzner, K. A. Gano, K. L. Imhoff, R. F. McCallum, D. A. Myers, T. L. Page, K. R. Price, J. V. Ramsdell, D. G. Rice, D. L. Schreiber, L. A. Skumatz, D. J. Sommer, J. J. Tawil, R. W. Wallace, and D. G. Watson. 1984. *Environmental Characterization of Two Potential Locations at Hanford for a New Production Reactor*. PNL-5275, Pacific Northwest Laboratory, Richland, Washington.

WCC. 1989. *Evaluation of Seismic Hazard for N-Reactor Facilities, Hanford Reservation, Hanford, Washington*. WHC-MR-0023, Prepared for Westinghouse Hanford Company by Woodward-Clyde Consultants, Oakland, California.

Westsik et al. 1984. *Characterization of Cement and Bitumen Waste Forms Containing Simulated Low-Level Waste Incinerator Ash*. NUREG/CR-3798, PNL-5153. U.S. Nuclear Regulatory Commission, Washington, D.C.

Westinghouse Hanford Company (WHC). 1992a. *Grout Treatment Facility Final Safety Analysis Report*. WHC-SD-WM-SAR-042, Rev. 0A. Westinghouse Hanford Company, Richland, Washington.

WHC. 1992b. *Quality Assurance Manual*. WHC-CM-4-2, Westinghouse Hanford Company, Richland, Washington.

WHC. 1992c. *Standard Engineering Practices*. WHC-CM-6-1, Westinghouse Hanford Company, Richland, Washington.

WHC. 1993a. *Prototype Surface Barrier at 200-BP-1 Operable Unit*. WHC-SD-EN-TI-142, Rev. 0. Prepared by Kaiser Engineers Hanford for Westinghouse Hanford Company, Richland, Washington.

WHC. 1993b. *Software Practices*. WHC-CM-3-10, Westinghouse Hanford Company, Richland, Washington.

Whiting, D. 1988. "Permeability of Selected Concretes." In *Permeability of Concretes*, ed. D. Whiting and A. Walitt, pp. 195-222. SP-108, American Concrete Institute, Detroit, Michigan.

Winograd, I. J., T. B. Coplen, J. M. Landwehr, A. C. Riggs, K. R. Ludwig, B. J. Szabo, T. P. Kolesar, and M. Revesz. 1992. "Continuous 500,000-Year Climate Record from Vein Calcite in Devils Hole, Nevada." *Science* 258:255-260.

Wittmeyer, G. W. and B. Sagar. 1992a. *INTRAVALE Project: Las Cruces Trench Solute Transport Modeling Study, Plot 2, Experiments A and B. Report for Research Activities for Calendar Year 1991*. W. C. Patrick, ed. CNWRA 91-01A. San Antonio, Texas.

Wittmeyer, G. W. and B. Sagar. 1992b. *INTRAVALE Project: Las Cruces Trench Unsaturated Flow Modeling Study, Plot 2, Experiment B. NRC High-Level Radioactive Waste Research at CNWRA for Calendar January 1 through June 30, 1992*. W. C. Patrick, ed. CNWRA 92-015. San Antonio, Texas.

Wood, D. E., R. U. Curl, T. E. Buhl, J. R. Cook, M. R. Dolenc, D. C. Kocher, B. A. Napier, K. W. Owens, E. P. Regnier, G. W. Roles, R. R. Seitz, D. J. Thorne and M. I. Wood. 1992. *Performance Assessment Task Team: Draft Progress Report*. DOE/LLW-157. Draft 0, September 1992, U.S. Department of Energy, Richland, Washington.

Woodruff, R. K., R. W. Hanf, M. G. Hefty, and R. E. Lundgren. 1991. *Hanford Site Environmental Report for Calendar Year 1990*. PNL-7930, Pacific Northwest Laboratory, Richland, Washington.

Woodruff, R. K., R. W. Hanf, and R. E. Lundgren. 1992. *Hanford Site Environmental Report for Calendar Year 1991*. PNL-8148, Pacific Northwest Laboratory, Richland, Washington.

Yates, S. R., M. Th. van Genuchten, A. W. Warrick, and F. J. Leij. 1992. "Analysis of Measured, Predicted, and Estimated Hydraulic Conductivity Using the RETC Computer Program." *Soil Sci. Soc. Am. J.* 56:347-354.

Performance Assessment of Grouted Double-Shell
Tank Waste Disposal at Hanford

Appendices A Through R

September 1994

A Westinghouse Hanford Company Report
Prepared by
Pacific Northwest Laboratory
and Westinghouse Hanford Company
for the U.S. Department of Energy

LIST OF APPENDICES

- Appendix A - Socioeconomics**
- Appendix B - Meteorology and Projection of Potential Future Climate for the Grout Project**
- Appendix C - Geology and Aquifer Characteristics of the Grout Treatment Facility**
- Appendix D - Ecology**
- Appendix E - Waste Inventory**
- Appendix F - Permanent Isolation Barrier and Warning Marker System**
- Appendix G - Detailed Description of PORFLOW**
- Appendix H - Verification and Benchmark Testing of the Flow and Transport Codes Used for the Hanford Grout Performance Assessment**
- Appendix I - GENII Computer Code**
- Appendix J - Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford**
- Appendix K - Status Report on Diffusion Through Asphalt**
- Appendix L - Measurement of Water Vapor Diffusion Through Asphalt Diffusion Barrier Material**
- Appendix M - Exposure Scenarios and Sources for Parameters**
- Appendix N - Sensitivity Analysis for Dose and Exposure Assessment Parameters**
- Appendix O - A Conceptual (Qualitative) Description of the Best Estimate Case**
- Appendix P - Additional Details of Data, Analysis, and Results**
- Appendix Q - Best Estimate Crack Predictions for the Grout Vault Engineered Barriers**
- Appendix R - Compilation of Responses to Requests for Further Information Made by the Peer Review Panel**

Appendix A

Socioeconomics^(a)

(a) This appendix was extracted from Section 4.5 of PNL-6415, Rev. 4. (C.E. Cushing, Editor. December 1991. *Hanford Site Environmental Policy Act (NEPA) Characterization*. PNL-6415, Rev. 4, Pacific Northwest Laboratory, Richland, Washington.)

Appendix A

Socioeconomics

Activity on the Hanford Site plays a dominant role in the socioeconomics of the Tri-Cities (Richland, Pasco, and Kennewick) and other parts of Benton and Franklin counties. The agricultural community also has a significant effect on the local economy. Major changes in Hanford activity would potentially affect the Tri-Cities and other areas of Benton and Franklin counties the most. Detailed analyses of the socioeconomics are found in Scott et al. (1987) and Watson et al. (1984).

A.1 Employment and Income

Three major sectors have been the principal driving forces of the economy in the Tri-Cities since the early 1970s: (1) the DOE and its contractors, operating the Hanford Site; (2) the Washington Public Power Supply System in its construction and operation of nuclear power plants; and (3) the agricultural community, including a substantial food-processing component. With the exception of a minor amount of agricultural commodities sold to local area consumers, the goods and services produced by these sectors are exported outside the Tri-Cities. In addition to the direct employment and payrolls, these major sectors also support a sizable number of jobs in the local economy through their procurement of equipment, supplies, and business services.

In addition to these three major employment sectors, three other components can be readily identified as contributors to the economic base of the Tri-Cities economy. The first of these, loosely termed "other major employers," includes five such employers: (1) Siemens Nuclear Power Corporation in North Richland, (2) Sandvik Special Metals in Kennewick, (3) Boise-Cascade in Wallula, (4) Burlington Northern Railroad, and (5) Iowa Beef Processors. The second component is tourism. The Tri-Cities area has increased its convention business substantially in recent years, in addition to business generated by travel for recreation. The final component in the economic base relates to the local purchasing power generated not from current employees but from retired former employees. Government transfer payments in the form of pension benefits constitute a significant proportion of total spendable income in the local economy.

A.1.1 DOE Contractors (Hanford)

Hanford continued to dominate the local employment picture with almost one-quarter of the total nonagricultural jobs in Benton and Franklin counties in 1991 (15,552 of 64,300). Hanford's payroll has a

widespread impact on the Tri-Cities and state economy in addition to providing direct employment. These effects are further described in Section A.2.

A.1.2 Washington Public Power Supply System

Although activity related to nuclear power construction ceased with the completion of the WNP-2 reactor in 1983, the Washington Public Power Supply System continues to be a major employer in the Tri-Cities area. Headquarters personnel based in Richland oversee the operation of one generating facility and perform a variety of functions related to two mothballed nuclear plants and one standby generating facility. In 1990, the Washington Public Power Supply System headquarters employed more than 1,700 workers. Washington Public Power Supply System activities generated a payroll of approximately \$71.6 million in the Tri-Cities during the year.

A.1.3 Agriculture

In 1990, agricultural activities in Benton and Franklin counties were responsible for approximately 12,000 jobs, or 16% of the area's total employment. According to the U.S. Department of Commerce's Regional Economic Information System, about 2,225 people were classified as farm proprietors in 1990. Farm proprietors' income from this same source was estimated to be \$80.9 million in the same year.

Crop and livestock production in the bicounty area generated about 7600 wage and salary jobs in 1990, as represented by the employees covered by unemployment insurance. The presence of seasonal farm workers would increase the total number of farm workers. Apart from the difficulty of obtaining reliable information on the number of seasonal workers, however, there is the question of how much of these earnings are actually spent in the local area. For this analysis, we assumed that the impact of seasonal workers on the local economy is sufficiently small to be safely ignored.

The area's farms and ranches generate a sizable number of jobs in supporting activities, such as agricultural services (e.g., application of pesticides and fertilizers, irrigation system development, etc.) and sales of farm supplies and equipment. These activities, often called "agribusiness," are estimated to employ 900 people.

Although formally classified as a manufacturing activity, food processing is a natural extension of the farm sector. More than 20 food processors in Benton and Franklin counties produce such items as potato products, canned fruits and vegetables, wine, and animal feed. Seasonally adjusted full-time employment in this sector averaged nearly 3,400 in 1989.

A.1.4 Other Major Employers

In 1990, other major employers--Siemens Nuclear Power Corporation, Sandvik Special Metals, Iowa Beef Processors, Boise Cascade, and Burlington Northern Railroad--employed approximately 3500 people in Benton and Franklin counties. Although Boise Cascade's Wallula mill lies outside both Benton and Franklin counties, most of its workforce resides in the Tri-Cities.

A.1.5 Tourism

In recent years, tourism has increased significantly in the Tri-Cities. According to the Tri-Cities Visitors and Convention Bureau, in 1989 nearly 700 conventions or tournaments were held in the Tri-Cities with about 59,900 visitors who spent an estimated \$13.9 million. In 1991, the Tri-Cities Visitors and Convention Bureau instituted a different reporting system, which now reports only the number of conventions held in the Tri-Cities; 170 conventions were held in 1991, with 29,795 attending visitors who spent an estimated \$9.4 million.

A study by the Washington State Department of Tourism estimated that overall tourism expenditures in the Tri-Cities were roughly \$77.5 million in 1990 and that travel-generated employment in Benton and Franklin counties was about 2,445 persons. In 1990, business travel associated with visitors on DOE business generated an estimated \$18.5 million payroll and roughly 2,445 jobs in the local economy. The Washington State Department of Tourism did not tabulate this information for 1991.

A.1.6 Retirees

Although the Benton and Franklin counties have a relatively young population (approximately 56% under the age of 35), 15,093 people over the age of 65 resided in Benton and Franklin counties in 1990. The portion of the total population that is 65 years and older is currently increasing at about the same rate as that being experienced by Washington State (3.0% and 3.1%, respectively). This segment of the population supports the local economy on the basis of income received from government transfer payments and pensions, private pension benefits, and prior individual savings.

The purchasing power of these senior citizens is an important component of the Tri-Cities economy just as for the entire nation. Taken as a whole, the estimated income of this component of the basic sector is roughly equivalent to the entire agricultural sector.

A.1.7 Secondary Sector

The secondary sector consists of all other workers in Benton and Franklin counties. A breakdown of nonagricultural wage and salary workers employed in Benton and Franklin counties in 1991 (Washington State Employment Security 1992) follows:

Industry		
Total manufacturing	5,800	(9%)
Transportation and public utilities	2,300	(4%)
Contract construction	3,600	(6%)
Wholesale and retail trade	13,400	(21%)
Finance, insurance, and real estate	1,800	(3%)
Services	25,500	(40%)
Government	11,900	(18%)

It should be noted that when 1991 annual averages are compared to 1990 annual averages, significant changes seem to have occurred in manufacturing (a loss of 8,200 jobs) and in services (a gain of 9,600). This change reflects a code change; there was no actual job loss or gain of this magnitude in those two categories.

Nonagricultural jobs increased by 2,300 during 1990 (a 3.6% growth rate). The year 1991 was the first time that nonfarm jobs (64,300) surpassed the previous peak of 63,940 nonfarm jobs recorded in 1981. Much of this increase can be accounted for by activities related to Hanford. Employment with DOE, the DOE contractors, the Washington State Power Supply System, and Siemens Nuclear Power Corporation provided the community with 17,594 jobs and an annual payroll of approximately \$711 million (Washington State Employment Security 1992).

A.2 Hanford and the Local and State Economy

In 1991, Hanford employment accounted directly for 24% of total nonagricultural employment in Benton and Franklin counties and slightly more than 0.6% of all nonagricultural statewide jobs. In 1991, Hanford Site operations directly accounted for an estimated 42% of the payroll dollars earned in the area.

Previous studies have revealed that each Hanford job supports about 1.2 additional jobs in the local service sector of Benton and Franklin counties (about 2.2 total jobs) and about 1.5 additional jobs in the state's service sector (about 2.5 total jobs) (Scott et al. 1987). Similarly, each dollar of Hanford income supports about 2.1 dollars of total local incomes and about 2.4 dollars of total statewide incomes. Based on these multipliers in Benton and Franklin counties, Hanford directly or indirectly accounts for more than 40% of all jobs.

Based on payroll records as of November 1, 1986, 92% of the direct employment and payroll of Hanford go to residents of Benton and Franklin counties. Nearly 80% of the employment and payroll go to residents who reside in one of the Tri-Cities. More than 45% of the payroll and employment go to

Richland residents, 27.7% to Kennewick residents, and 9.5% to Pasco residents. West Richland, Benton City, Prosser, and other areas in Benton and Franklin counties account for 11.5% of total employment and payroll.

Hanford and contractors spent nearly \$154 million, or 47.5% of total procurements of \$324 million, initially through Washington firms in 1986. About 18% of Hanford orders were filled by Tri-Cities firms. In many cases, these procurements filled by Tri-Cities firms only result in retail and wholesale markups; however, a significant portion of all Hanford orders, \$6.6 million, are placed directly to Washington manufacturers.

Contractors spent \$22 million on electricity and other utilities in 1986, ordered nearly \$19 million in business services, and spent \$73 million on Washington retail and wholesalers. Finally, DOE and its contractors provided about \$16 million (mainly in grants) to local governments and others for a variety of public purposes.

Hanford contractors paid a total of \$10.9 million in FY 1988 in state taxes on operations and purchases. Estimates show that Hanford employees paid \$27.0 million in state sales tax, use taxes, and other taxes and fees in FY 1988. In addition, Hanford paid \$0.9 million to local government in Benton, Franklin, and Yakima counties in local taxes and fees (Scott et al. 1989).

A.3 Demography

Estimates by the U.S. Bureau of the Census for 1990 (U.S. Department of Commerce 1991) placed the population totals for Benton and Franklin counties at 112,560 and 37,473, respectively. When compared to the 1980 census data in which Benton County had 109,444 residents and Franklin County's population totaled 35,025, the 1990 Census figures reflect the current growth occurring in these two counties. The current population totals for Benton and Franklin counties are slightly higher than those recorded in 1982, which represents the period with the highest population (an estimated 111,700 residents in Benton County and 36,200 residents in Franklin County).

Within each county, the 1990 estimates distribute the Tri-Cities population as follows: Richland, 32,315; Kennewick, 42,159; and Pasco, 20,337. The combined populations of Benton City, Prosser, and West Richland totaled 10,244 in 1990. The unincorporated population of Benton County was 27,842. In Franklin County, incorporated areas other than Pasco have a total population of 2,424. The unincorporated population of Franklin County was 14,712.

The 1990 estimates of racial categories by the Bureau of the Census indicate that, in Benton and Franklin counties, Asians represent a lower proportion and individuals of Hispanic origin represent a higher proportion of the racial distribution than those in the state of Washington. Countywide, Benton and Franklin counties exhibit varying racial distributions.

Benton and Franklin Counties account for 3% of Washington State's population (U.S. Department of Commerce 1991). Unlike previous years, Benton and Franklin Counties population demographics are quite similar to those found within the state of Washington. Fifty-six percent of the population of Benton and Franklin counties is under the age of 35, compared to 54% for the state of Washington. Within the state of Washington, 25- to 34-year-olds constitute the largest age group (17.6%) compared to 16.3% found within Benton and Franklin counties. In general, the population of Benton and Franklin counties is somewhat younger than that of Washington State. The 0- to 4-year-old age group accounts for 8.5% of the total bicounty population as compared to 7.5% for Washington State. The 65-year-old and older age group constitutes 10% of the population of Benton and Franklin counties compared to 12.0% for the state of Washington.

A.4 Transportation

The Tri-Cities serve as a regional transportation and distribution center with major air, land, and river connections. The Tri-Cities have direct rail service, provided by Burlington Northern and Union Pacific, that connects the area to more than 35 states. The Washington Central Railroad serves eastern Washington as well. Union Pacific operates the largest fleet of refrigerated rail cars in the United States and is essential to food processors that ship frozen food from this area. Passenger rail service is provided by Amtrak, which has a station in Pasco.

Docking facilities at the Ports of Benton, Kennewick, and Pasco are important aspects of this region's infrastructure. These facilities are located on the 525-km-long commercial waterway, which comprises the Snake and Columbia rivers, that extends from the Ports of Lewiston-Clarkston in Idaho to the deep-water ports of Portland, Oregon, and Vancouver, Washington. The average shipping time from the Tri-Cities to these deep-water ports by barge is 36 hours (Evergreen Community Development Association 1986).

Daily air passenger and freight services connect the area with most major cities through the Tri-Cities Airport, located in Pasco. The airport is currently served by one national and two commuter-regional airlines. There are two runways, a main and minor crosswind. The main runway is equipped for precision instrumentation landings and takeoffs. Each runway is 7,700 ft long and 150 ft wide, and can accommodate landings and takeoffs by medium-range commercial aircraft, such as the Boeing 727-200 and Douglas DC-9. The Tri-Cities airport handled about 160,844 passengers (enplanements) in 1991, an increase of approximately 6% from 1990. Projections indicate that the recently expanded terminal can serve almost 300,000 passengers annually. Two additional airports, located in Richland and Kennewick, are limited to serving private aircraft.

The Tri-Cities are linked to the region by five major highways. Route 395 joins the area with Spokane to the northeast. Both it and Route 240, which crosses through the Hanford Site, connect with Interstate 90 to the north. Route 12 links the region with Yakima to the northwest; with Lewiston, Idaho,

to the east; and with Walla Walla to the southeast. The area is also linked to Interstate 84 to the south, via Interstate 82, and Route 14 and Interstate 82 also connect the area to the Yakima Valley and Interstate 90 in Ellensburg. Routes 240 and 24 traverse the Hanford Site and are maintained by Washington State. Other roads within the reservation are maintained by the DOE.

A.5 Police and Fire Protection

Police protection in Benton and Franklin counties is provided by Benton and Franklin counties' sheriff departments, local municipal police departments, and the Washington State Patrol Division headquartered in Kennewick.

Table A.1 indicates the number of fire-fighting personnel, both paid and unpaid, on the staffs of fire districts in the area.

A.5.1 Hanford Fire Station

The Hanford Fire patrol, composed of 126 firefighters, is trained to dispose of hazardous waste and to fight chemical fires. During the 24-hour duty period, 5 firefighters cover the 1100 Area, 7 protect the 300 Area, 7 watch the 200-East and 200-West Areas, 6 are responsible for the 100 Area, and 6 cover the 400 Area, which includes the WPPSS area. To perform their responsibilities, each station has access to a Hazardous Material Response Vehicle that is equipped with chemical fire extinguishing equipment, an attack truck that carries foam, halon, and Purple-K dry chemical, a mobile air truck that provides air for respiratory protection; and a transport tanker that supplies water to six trucks used for fighting brush fires. They have five ambulances and contact with local hospitals.

Table A.1. Fire Protection in the Tri-Cities, 1992

	Fire Fighting Personnel	Volunteers	Total	Service Area
Kennewick	42	0	42	City of Kennewick
Pasco	30	0	30	City of Pasco
Richland	45	0	45	City of Richland
BCRFD 1	2	120	122	Kennewick Area
BCRFD 2	1	28	29	Benton City
BCRFD 4	2	28	30	West Richland

Source: Personal communication with each department office, June 1992.

A.6 Utilities

A.6.1 Water

The principal source of water in the Tri-Cities and the Hanford Site is the Columbia River, from which the water systems of Richland, Pasco, and Kennewick draw a large portion of the average 11.38 billion gallons used in 1991. Each city operates its own supply and treatment system. The Richland water supply system derives about 67% of its water from the Columbia River, approximately 15%-20% from a well field in North Richland, and the remaining from groundwater wells. The city of Richland's total usage in 1991 was 5.65 billion gallons. This current usage represents approximately 58% of the maximum supply capacity. The city of Pasco system likewise draws from the Columbia River for its water needs. The 1991 estimate of consumption is 2.81 billion gallons. The Kennewick system uses two wells and the Columbia River for its supply. These wells serve as the sole source of water between November and March and can provide approximately 62% of the total maximum supply of 7.3 billion gallons. Total usage in 1991 was 2.92 billion gallons.

The major incorporated areas of Benton and Franklin counties are served by municipal wastewater treatment systems, whereas, the unincorporated areas are served by onsite septic systems. Richland's wastewater treatment system is designed to treat a total capacity of 27 million m³/yr [a daily average flow of 8.9 million gallons per day (mgd) with a peak flow of 44 mgd]. In 1991, the system processed an average of 4.83 mgd. The Kennewick system similarly has significant excess capacity; with a treatment capability of 12 million m³/yr, or 8.7 mgd, 1991 usage was 4.8 mgd. Pasco's waste-treatment system processes an average of 2.22 mgd, while the system could treat 4.25 mgd or 34.6 million m³/yr.

A.6.2 Electricity

In the Tri-Cities, electricity is provided by the Benton County Public Utility District, Benton Rural Electrical Association, Franklin County Public Utility District, and City of Richland Energy Services Department. All the power that these utilities provide in the local area is purchased from the Bonneville Power Administration (BPA), a federal power marketing agency. The average rate for residential customers served by the three local utilities is approximately \$0.0396/kWh. Electrical power for the Hanford Site is purchased wholesale from BPA. Energy requirements for the Site during FY 1988 exceeded 550 average MW.

Natural gas, provided by the Cascade Natural Gas Corporation, serves a small portion of residents, with 4,800 residential customers in June 1992.

In the Pacific Northwest, hydropower, and to a lesser extent, coal and nuclear power, constitute the region's electrical generation system. Total nameplate generating capacity is about 40,270 MW. Approximately 74% of the region's installed generating capacity is hydroelectric, which supplies approximately

65% of the electricity used by the region. Coal-fired generating capacity is 6,702 MW in the region, or 16% of the region's electrical generating capacity. Two commercial nuclear power plants are in service in the Pacific Northwest, with a 2247-MW capacity or 6% of the region's generating capacity. Oil and natural gas account for about 3% of capacity.

The region's electrical power system, more than any other system in the nation, is dominated by hydropower. On average, the region's hydropower system can produce 16,400 MW. Variable precipitation and limited storage capabilities alter the system's output from 12,300 average MW under critical water conditions to 20,000 average MW in record high water years. The Pacific Northwest system's reliance on hydroelectric power means that it is more constrained by the seasonal variations in peak demand than in meeting momentary peak demand.

Throughout the 1980s, the Northwest had more electric power than it required and was operating with a surplus. This surplus has been exhausted, however, and there is only approximately enough power supplied by the existing system to meet the current electricity needs. Hydropower improvement projects currently under construction in the Northwest include about 150 MW of new capacity. The cost and availability of several other resources are currently being studied (Northwest Power Planning Council 1986).

A.7 Land Use

The Hanford Site encompasses 1,450 km² (560 mi²) and includes several DOE operational areas. The major areas are as follows:

- The entire Hanford Site has been designated a National Environmental Research Park (NERP).
- The 1(X) Areas, bordering on the right bank (south shore) of the Columbia River, are the sites of the eight retired plutonium production reactors and the N Reactor, which is currently in wet layup. The 1(X) Areas occupy about 11 km² (4.2 mi²).
- The 2(X)-West and 2(X)-East Areas are located on a plateau about 8 and 11 km (5 and 6.8 mi), respectively, from the Columbia River. These areas have been dedicated for some time to fuel reprocessing and waste processing management and disposal activities. The 2(X) Areas cover about 16 km² (6.2 mi²).
- The 3(X) Area, located just north of the City of Richland, is the site of nuclear research and development. This area covers 1.5 km² (0.6 mi²).

- The 400 Area is about 8 km (5 mi) north of the 300 Area and is the site of the Fast Flux Test Facility used in the testing of breeder reactor systems. Also included in this area is the Fuels and Material Examination Facility.
- The 600 Area includes all of the Hanford Site not occupied by the 100, 200, 300, or 400 Areas. Land uses within the 600 Area include:
 1. 310 km² (120 mi²), known as the Arid Land Ecology Reserve (ALE), which has been set aside for ecological studies.
 2. 4 km² (1.5 mi²) leased by Washington State, a part of which is used for commercial low-level radioactive waste disposal.
 3. 4.4 km² (1.7 mi²) for Washington Public Power Supply System nuclear power plants.
 4. 2.6 km² (1 mi²) transferred to Washington State as a potential site for the disposal of nonradioactive hazardous wastes.
 5. About 130 km² (50 mi²) under revocable use permit to the U.S. Fish and Wildlife Service for a wildlife refuge.
 6. 225 km² (87 mi²) under revocable use permit to the Washington State Department of Game for recreational game management.
 7. Support facilities for the controlled access areas.

An area of 665 km² (257 mi²) has been designated for ALE, the U.S. Fish and Wildlife Service, wildlife refuges, and the Washington State Department of Game management area (U.S. DOE 1986).

Land use in other areas includes urban and industrial development, irrigated and dry-land farming, and grazing. In 1985, wheat represented the largest single crop in terms of area planted in Benton and Franklin counties with 116,000 hectares (290,000 acres). Corn, alfalfa, hay, barley, and grapes are other major crops in Benton and Franklin counties.

In 1986, the Columbia Basin Project, a major irrigation project to the north of the Tri-Cities, produced gross crop returns of \$343 million, representing 19% of all crops grown in Washington State. In 1986, the average gross crop value per irrigated acre was \$664.00. The largest percentage of irrigated acres produced alfalfa hay, 29.4% of irrigated acres; wheat, 15.0%; and corn (feed grain), 9.4%. Other significant crops are potatoes, apples, dry beans, asparagus, and pea seed.

A.8 Offsite Historical and Cultural Sites

Currently, 16 archaeological properties are located near the Hanford Site. These properties are listed in the National Register of Historic Places.

A.9 References

Evergreen Community Development Association. 1986. *Tri-Cities Enterprise Center Business Development Plan*. Evergreen Community Development Association, Richland, Washington.

Northwest Power Planning Council. 1986. *Northwest Energy News*, April/May 1986, Vol. 5, No. 3, Portland, Oregon.

Scott, M. J., D. B. Belzer, R. J. Nesse, R. J. Schultz, P. A. Stokowski, and D. C. Clark. 1987. *The Economic and Community Impacts of Closing Hanford's N Reactor and Nuclear Materials Production Facilities*. PNL-6295, Pacific Northwest Laboratory, Richland, Washington.

Scott, M. J., D. B. Belzer, S. J. Marsh, D. M. Beck, R. W. Schultz, and S. A. Harkreader. 1989. *Hanford and the Tri-Cities Economy: Review and Outlook, March 1989*. PNL-6813, Pacific Northwest Laboratory, Richland, Washington.

U.S. Department of Commerce. 1991. *1990 U.S. Census of Population and Housing, State and County Profiles, Washington* (Summary Tape File 1A for Washington State). Office of Financial Management, U.S. Department of Commerce, Washington, D.C.

U.S. Department of Energy (DOE). 1986. *Environmental Assessment, Reference Repository Location, Hanford Site, Washington*. DOE/RW-0070, U.S. Department of Energy, Washington, D.C.

Washington State Employment Security. 1992. *Washington State Labor Area Summaries*, Vol. 7, No. 3. Washington State Employment Security Labor Market and Economic Analysis Branch, Olympia, Washington.

Watson, E. C., C. D. Becker, R. E. Filzner, K. A. Gano, C. L. Imhoff, R. F. McCallum, D. A. Myers, T. L. Page, K. R. Price, J. V. Ramsdell, D. G. Rice, D. L. Schreiber, L. A. Skumatz, D. J. Sommer, J. J. Tawil, R. W. Wallace, and D. G. Watson. 1984. *Environmental Characterization of Two Potential Locations at Hanford for a New Production Reactor*. PNL-5275, Pacific Northwest Laboratory, Richland, Washington.

Appendix B

Meteorology and Projection of Potential Future Climate for the Grout Project

Appendix B

Meteorology and Projection of Potential Future Climate for the Grout Project

K. L. Petersen, Westinghouse Hanford Company

B.1 Introduction

The Hanford Site is located in the Pasco Basin in south-central Washington. The climate of this area can be classified as midlatitude semiarid or midlatitude desert, depending on the climatological classification scheme being used. Summers are warm and dry with abundant sunshine. Large diurnal temperature variations are common during this season, resulting from intense solar heating and nighttime cooling. Daytime high temperature in June, July, and August can exceed 40°C. Winters, on the other hand, are cool with occasional precipitation. Outbreaks of cold air associated with modified arctic air masses infrequently reach the area and cause temperatures to drop below -18°C. Overcast skies and fog occur periodically in this season.

Understanding the underlying causes of this modern climatic pattern in the Pasco Basin provides a basis for evaluating past and especially potential future changes that might be important in any relatively long-term performance assessment. In addition, historic characteristics of extreme events and changes of seasonality ultimately may give additional insight to the important controlling variables to be considered. The following sections address the modern climatic patterns, the climate patterns of the recent past, Holocene paleoclimate patterns, the Milankovitch theory of global climate change, the greenhouse theory of climate change, and predictions of future climate change for the Pasco Basin.

B.2 Modern Climatic Patterns

The Pasco Basin is in the rain shadow of the Cascade Range. These mountains limit much of the maritime influence of the Pacific Ocean, producing a climate that is more continental in nature than if the mountains were not there. The local topographic features have significant effect on temperature, wind, and precipitation because all air masses that reach the Pasco Basin undergo some modification following their passage over the relatively complex topography of the area. The climate of the Hanford Site within the Pasco Basin is greatly influenced by the Cascade Mountains beyond Yakima to the west. In addition to providing a rain shadow effect, this range also serves as a source of cold air drainage, which has a considerable effect on the wind regime at the Hanford Site.

Climatological data are available for the Hanford Meteorological Station (HMS), which is located between the 200 East and 200 West Areas situated on a plateau at about 215 m elevation. The plateau slopes downward toward the Columbia River at roughly 105 m elevation about 16 km to the north and slopes upward to the foothills of the Rattlesnake Mountains about 16-km south. Data have been collected at this location since 1945. Temperature and precipitation data are also available from nearby locations for the period 1912 through 1943. A summary of these data through 1980 has been published by Stone et al. (1983). Data from the HMS are representative of the general climatic conditions for the region and describe the specific climate of the 200 Area plateau. Local variations in the topography of the Hanford Site may cause some aspects of climate at portions of the Hanford Site to differ significantly from those of the HMS. For example, winds near the Columbia River are different than those at the HMS. Similarly, precipitation along the slopes of the Rattlesnake Hills differs climatically from that at the HMS.

B.2.1 Temperature

Diurnal and monthly averages and extremes of temperature are presented in Stone et al. (1983). Average monthly temperature at the HMS is 12°C. The unusually cool nights that do occur result from cool gravity winds originating from the Cascade Mountains. Temperatures at Hanford are colder in the winter and warmer in the summer than would be the case without the Cascades blocking the more equitable maritime climate to the west. The Pasco Basin is warmer during the winter than a site at an equivalent latitude on the Great Plains in the midcontinent because mountain ranges to the north and east shield the area from many of the arctic surges that descend out of Canada. Half of all winters are free of temperatures of -18°C or lower.

Ranges of daily maximum and minimum temperatures vary from normal maxima of 2°C in early January to 35°C in late July. There are, on the average, 55 days during the summer months with maximum temperatures greater than or equal to 32°C and 13 days with maxima greater than or equal to 38°C. From mid-November through mid-March, minimum temperatures average less than or equal to 0°C with the minima in early January averaging -6°C. During the winter, there are, on average, 4 days with minimum temperatures less than or equal to -18°C; however, only about one winter in two experiences such temperatures. The record maximum temperature is 46°C, and the record minimum temperature is -33°C. For the period 1912 through 1980, the average monthly temperatures range from a low of -2°C in January to a high of 25°C in July. During the winter, the highest monthly average temperature at the HMS was 7°C and the record lowest was -6°C, both occurring during February. During the summer, the record maximum monthly average temperature was 28°C (in July), and the record lowest was 17°C (in June).

B.2.2 Precipitation

Measurements of precipitation have been made at the HMS since 1945. Average annual precipitation at the HMS is 16 cm. The 3 months of November through January contribute 44% of this total, while the 3 months of July through September contribute only 13%. On the average there are only

2 occurrences per year of 24-hour amounts of precipitation of 1.27 cm or more. Rainfall intensities of 1.27 cm/h persisting for 1 hour are expected once every 10 years. Occurrences of 24-hour amounts of precipitation of 5.08 cm or more number only 2 in the entire 35 years of record (1946-1980). One of these was the record storm of October 1-2, 1957, in which rainfall totalled 2.74 cm in 3 hours, 4.27 cm in 6 hours, and 4.78 cm in 12 hours.

About 38% of all precipitation during the months of December through February is in the form of snow. Winter monthly average snowfall ranges from 0.8 cm in March to 13.5 cm in January. Only 1 winter in 4 is expected to experience an accumulation of as much as 15.24 cm of snow on the ground. The average seasonal number of days with 15.24 cm in. or more of snow on the ground is 4, although the 1964-1965 winter had 35 days with snow on the ground, 32 of which were consecutive. That winter also provided one of the greatest snow depths, with 30.7 cm of snow occurring in December 1964. The record greatest depth of snow on the ground is 62.2 cm in February 1916.

Based on extreme value analysis of records from 1947 through 1969, the average return period and existing record for various precipitation amounts and intensity during specified time periods at Hanford suggest the following. A 60-minute 100-year storm would produce 2.06 cm of precipitation and a 60-minute 1000-year storm would produce 2.82 cm. Rainfall intensities of 2.5 cm/h for 1 hour are expected only once every 500 years. No records have been kept for time periods less than 60 minutes; however, the rain gauge chart for June 12, 1969 shows that 1.40 cm occurred during a 20-minute period. A 24-hour maximum accumulation for a 100-year return period is estimated to be 5.05 cm and the 1000-year return is 6.81 cm.

B.2.3 Severe Weather

High winds are also associated with thunderstorms. The average occurrence of thunderstorms is 10 per year. They are most frequent during the summer; however, they have occurred in every month. The average winds during thunderstorms do not come from any specific direction. Estimates of the extreme winds, based on peak gusts observed from 1945 through 1980, are given in Stone et al. (1983) and are shown in Table B.1. Using the National Weather Service criteria for classifying a thunderstorm as "severe" (i.e., hail with a diameter equal to or greater than 20 mm or wind gusts of 93 km/h or greater), only 1.9% of all thunderstorm events observed at the HMS have been "severe" storms, and all met the classification criteria based on wind gusts.

Tornadoes are infrequent and generally small in the northwest portion of the United States. Grazulis (1984) does not list any violent tornadoes for the region surrounding Hanford (U.S. DOE 1987). The HMS climatological summary (Stone et al. 1983) and the National Severe Storms Forecast Center (NSSFC) database list 22 separate tornado occurrences within 161 km of the Hanford Site from 1916 through August 1982. Two additional tornadoes have been reported since August 1982.

Table B.1. Estimates of Extreme Winds at Hanford Site

Return Period, yr	Peak Gusts, km/h	
	15.2 m Above Ground	61 m Above Ground
2	97	109
10	114	129
100	137	151
1000	159	75

Using the information in the preceding paragraph and the statistics published in Ramsdell and Andrews (1986) for the 5° block centered at 117.5° west longitude and 47.5° north latitude (the area in which the Hanford Site is located), the expected pathlength of a tornado on the Hanford Site is 7.6 km, the expected width is 95 m, and the expected area is about 1.5 km². The estimated probability of a tornado striking a point at Hanford, also from Ramsdell and Andrews (1986), is 9.6×10^{-6} /yr. The probabilities of extreme winds associated with tornadoes striking a point can be estimated using the distribution of tornado intensities for the region. Table B.2 gives these probability estimates.

B.2.4 Historic Climate Patterns

To see how characteristic the modern climatic conditions are to the Pasco Basin, it is valuable to look at regional patterns for a reasonable length of time into the past. Climatic variation refers to systematic changes of temperature, precipitation, and other climatic variables during the past 100 years as

Table B.2 Estimate of the Probability of Extreme Winds Associated with Tornadoes Striking a Point at Hanford^(a)

Wind Speed, km/h	Probability per Year
1(X)	2.6×10^{-6}
2(X)	6.5×10^{-7}
3(X)	1.6×10^{-7}
4(X)	3.9×10^{-8}

(a) Ramsdell and Andrews (1986).

revealed in historical series of quantitative meteorological observations (Mitchell 1987). Climatic variation specifically refers to changes of average climate between periods, each of which was decades or more in length. The current practice is to take 30-year periods (three adjacent decades), calculate the statistical characteristics of that period, and define the statistics as describing the "30-year normal" climate for the weather station. A new 30-year normal is calculated with the completion of each new decade by averaging that decade with the prior two decades. The variation in climate is thus the contrast between two non-overlapping normal periods. Slower climatic changes with periods of time comparable to the length of available observations are known as secular variations.

As partly described above, the current climate of southeastern Washington is characterized by relatively cold and wet winters with a relatively dry summer. Upon closer examination it is found that eastern Washington also has a secondary spring precipitation maximum (Stone et al. 1983; Quinn 1977) which appears to be the result of an overlay of a Plains-like precipitation pattern. For instance, Missoula, Montana, is characterized by high spring and low winter precipitation, with very cold winters. On the other hand, the climate pattern to the west of the Pasco Basin on the coast is characterized by a winter precipitation pattern with a little or no spring secondary precipitation maximum. The coastal or Seattle-like weather is also characterized by mild winters. The overlap of these two contrasting patterns located to the east and west of the Pasco Basin seem to best explain the Pasco Basin pattern.

On a decadal scale, however, precipitation and temperature patterns in the Pasco Basin have tended to alternate between those that are more continental-like and with a more pronounced spring peak (i.e., similar to Missoula, Montana) and those of a more equitable coastal area with a depressed or missing spring peak (i.e., similar to Seattle) (Coatley 1979; Balling and Lawson 1982; Heerman et al. 1971; Ruffner and Bair 1977). These two distinct climate patterns also have distinctive vegetation associated with them. In the northwestern United States, lowland, treeless areas with a spring precipitation maximum are usually characterized by relatively shallow-rooted grasses, whereas areas with a winter precipitation maximum are characterized by more deeply rooted shrubs such as sagebrush (Daubenmire 1970; Risser et al. 1981).

Evidence that historically there have been swings between patterns more representative of Seattle or Missoula are important because fossil pollen analyses covering the last 10,000 years or so suggest the occurrence of an alternating dominance between grass and sagebrush in eastern Washington in the past (this will be discussed in more detail). Such changes may provide clues to the potential direction of future climatic changes as a result of climatic cycles (see section B.5) or as a result of the "greenhouse effect" (see section B.6).

B.3 Climate Pattern of the Recent Past

Instrumental records in the Pacific Northwest do not go back much beyond 100 years. To investigate climatic change prior to that time, researchers have relied on the use of proxy climate records.

Recent changes in a number of proxy climate records have indicated that there probably have been changes in the pattern of climate in the Pacific Northwest. Dendroclimatic reconstructions using tree-ring analysis have been useful in determining climate patterns for time periods of decades to hundreds of years. Trees in temperate regions produce annual growth layers or rings that often display common year-to-year variability in size, structure, and chemical composition (Fritts 1976). Because climate is the principal driver of growth-ring variability common to many trees in an area, it is possible to reconstruct year-to-year climatic records from growth rings.

Cropper and Fritts (1986) and Gramulich (1987) authored studies that are of particular interest for characterizing recent climatic patterns in the Pacific Northwest. Cropper and Fritts (1986) derived a 360-year regional reconstruction of seasonal and annual variations in temperature and precipitation from statistical relationships between meteorological records from Columbia Basin stations and tree-ring data from throughout western North America. Using similar methods, Gramulich (1987) compared 300-year precipitation reconstructions for three regions in the Pacific Northwest. Gramulich used subsets of records from a network of meteorological stations and tree-ring data from each region.

Cropper and Fritts (1986) calibrated the relationship between Columbia Basin weather records and a network of 65 tree-ring chronologies by applying canonical stepwise multiple regression to principal components of tree growth indices and principal components of climate. The best of the network of reconstructions were averaged to produce regional reconstructions. The results suggest that the average temperature of the Columbia Basin for the last three centuries was slightly higher (0.09°C) and more variable (4% higher standard deviation) than the 20th Century. The increase was primarily attributed to warmer winters. The reconstructions also suggest that the last three centuries were wetter on the average (0.81 cm), primarily in the autumn. Furthermore, droughts were apparently more frequent starting in the second half of the 17th Century and lasted longer than droughts of the 20th Century.

Gramulich (1987) also used multiple regression models to reconstruct precipitation in the Pacific Northwest. The results indicate that the average precipitation of the 18th and 19th Centuries did not differ from the average precipitation of the 20th Century. The reconstructions also indicate that extreme drought years, caused by high-pressure ridges shifting storm tracks to the north during normally wet winter months, were common to all regions in the Pacific Northwest.

An early 19th Century wet period in the Columbia Basin was a time of extended drought in southern Oregon and northern California, and while the Columbia Basin was experiencing a late 19th Century drought, southern Oregon and northern California were wetter than normal. Gramulich (1987) attributes these contrasting north-south patterns to latitudinal variation in the position of the polar jet stream in the winter and subtropical high pressure cells in the summer. The long-term average position of these local climate drivers will likely be impacted by global climatic change in the future.

In another kind of study, Burbank (1982) correlated climate, mass balances, and glacial fluctuations at Mount Rainier in the Washington Cascades since 1850 and concluded that based on the analyses of the reconstructed temperature record and former ice frontal positions that as much as a 1°C temperature rise occurred between 1770 and 1830.

B.4 Holocene Paleoclimate Patterns

Detailed paleoecological and paleoclimatic studies are assuming increased importance as modern science attempts to predict the impact of global climate change and assess the long-term performance capabilities of hazardous and nuclear waste facilities. Chatters (1991), Chatters and Hoover (1992), and unpublished data summarize existing proxy evidence for climatic and ecological change in the Columbia Basin of northwestern America for the last 10,000 to 13,000 years. Inferences based on glacial and fluvial geomorphology, cave and lacustrine sedimentation patterns, palynology, fossil timberlines, subfossil paleontology, and stable isotope study of inland lakes are integrated into a detailed record of environmental change. Findings identify a terminal Pleistocene environment kept cool and dry by masses of ice and glacial meltwater, supporting a mosaic of now-allopatric plant and animal communities. This was followed between 10,000 and 8,500 years ago by a period of warmer-than-modern summers, colder-than-modern winters and low, but spring dominant precipitation, supporting extensive grasslands and the faunas associated with them. By 8,000 years ago summers and winters were both relatively warm, and precipitation was at least 33% below modern levels. This climate pattern resulted in reduced stream flows with late spring flow maxima and extensive development of shrub-steppe vegetation throughout most of the region.

Chatters et al. (1991) further characterize the effect the climate of 6,000 and 8,000 years ago had on streams and rivers of the region:

- stream flows were less than 70% modern
- many small, low elevation, perennial streams became intermittent (dry during part of the year)
- streams had finer bed loads (greater sedimentation)
- water temperatures were higher
- the spring peak flow (freshet) ended three to four weeks earlier than it does today.

Such conditions would be expected to be produced by a climate that was warmer than that of today, with less precipitation, and with a higher percentage of annual precipitation falling as winter rain. Such changes of climatic conditions, if they were to happen in the future, could be important to consider when doing a performance assessment.

Chatters (1991) indicates climate cooled but remained dry between 5,400 years and 4,500 years ago, then underwent a period of transition to wetter, cooler conditions between 4,500 years and 3,900 years ago. Rivers flooded frequently, and forests expanded into steppe zones. From 3,900 years until 2,400 years ago the climate was cool in summer and cold in winter, with winter-dominant precipitation at least 30% above modern amounts. Alpine glaciers underwent the first synchronous advance of the Holocene. Rivers stabilized, and their peak flows were delayed into mid-summer; steppe vegetation increased in density as subalpine and probably montane forests expanded beyond their modern margins. Warmer, drier conditions returned between 2,400 years and 2,000 years ago, reducing vegetation density and bringing a renewal of severe flooding. Climate then improved somewhat, and modern climates were established. The Little Ice Age, although evident in alpine cirques, had little apparent effect on regional environments except for a slight drying around 550 years ago.

Although the above synthesis is detailed, data are lacking for important geographic areas, and most paleoclimatic variables cannot yet be quantified with precision. Studies outlined in Petersen et al. (1992) are designed to improve on this reconstruction.

B.5 Milankovitch Theory of Global Climatic Change

Among climatologists, it is universally accepted that global climates have undergone significant variation in the past, and there is every reason to expect that such natural variations will continue into the future (Crowley and North 1991). The study of deep-sea sediments in recent years has yielded persuasive evidence that the recurring ice ages characteristic of the past million years are indeed closely associated with the so-called Milankovitch cycles (Earth Systems Sciences Committee 1988). These cycles (related to slow changes in the distance and in the Earth's polar orientation to the sun) cause subtle, but apparently critical, changes in the seasonal variation of the incoming solar radiation, particularly in high latitudes. And these cycles may be reliably calculated from celestial mechanics. The waxing and waning of the ice ages themselves are recorded in the ratio of oxygen isotopes in deep-sea sediments, because the reduced fraction of heavy isotopes in freshwater evaporated at the ocean surface is reflected in an enhanced ratio in the precipitated carbonate skeletons of microorganisms living in the remaining sea water. Although there are still some issues of interpretation and dating, variation in the stable oxygen isotope ratios of $^{18}\text{O}/^{16}\text{O}$ with depth in an ocean sediment core are widely interpreted as measuring total land-ice volume as a function of the passage of time. As more informative cores have been examined and dating procedures have become more refined, it has become more apparent that the changes in insolation and subsequent changes in ice volume are highly correlated. However, a correspondence between the two records

requires an allowance for the slow buildup of ice sheets over several tens of thousands of years (as contrasted with their relatively rapid decay), which introduces a degree of nonlinearity (not a one-to-one relationship) into the system of responses.

According to the Milankovitch theory, over the last 800,000 years and possibly for as long as the last 2,000,000 years the earth has experienced a number of glacial cycles, each about 100,000 years in length with a 10,000- year-long interglacial (Hays et al. 1976; Kukla 1981; Berger et al. 1984). The last interglacial/glacial cycle started with a 10,000-year-long interglacial (deep sea core oxygen isotope stage 5e) about 125,000 years ago, immediately followed by a rapid growth of global ice sheets beginning at 115,000 years ago. Glacial climate dominated the earth until about 12,000 years ago when continental ice retreated from its most southern extent into what is now the state of Washington.

No vegetation on earth escaped the repeated stress of these climates and interglacial adjustments, and the Pasco Basin of south central Washington is no exception. With each glacial cycle, the species displaced by climate, ice, water, and competition responded through growth form, migration or selection, or faced local extinction. Based on the geophysical evidence of the past, there is a strong suggestion that we are cycling into the next glacial period (Imbrie and Imbrie 1980; Berger 1981; Berger et al. 1984).

More and more evidence is being amassed to show that at particular times, climate change seems to have occurred abruptly (Berger and Labeyrie 1987). For example, during the extreme of the full glacial about 18,000 years ago, Canada was covered with ice. A summer radiation minimum corresponded with the maximum expansion of continental glaciers (Imbrie and Imbrie 1980) that will be referred to as the full glacial in the following discussion. Field data suggest that as compared to today the principal features of full glacial climate were the strong summer cooling and the expansion of winter precipitation from Pacific frontal storms and greatly diminished monsoonal flow. Computer simulation experiments of full glacial climates by COHMAP (COHMAP Members 1988) and Manabe and Broccoli (1985) suggest that the very presence of the Laurentide ice sheet thrust up into the lower atmosphere acted as a physical barrier and split the jet stream into two branches, like a boulder in a stream. The COHMAP simulations suggest that the mean position of the southerly branch was 20 degrees south of the modern position of the jet stream and the summer monsoon was essentially nonexistent in the western United States. The very existence of a vast, very cold, and elevated ice sheet created a perpetual high-pressure system with cold, dense sinking-air swirling clockwise that most likely would have placed the Pacific Northwest under easterly anticyclonic flow off the ice sheet (a complete reversal in dominant westerly air flow of today). Summer temperatures in the Pacific Northwest may have been as much as 5-10°C below the modern mean (Barnosky et al. 1987). Future projections of temperature increase with the greenhouse effect is approaching that same magnitude of change, but it is to occur in as little as 100 years (see section B.6).

During the full glacial, the Hanford site region was affected by past catastrophic flooding. Floods that have could have affected the Hanford Site can be conveniently placed in three types according to size: Type I consists of floods resulting from precipitation or snowmelt without drainage from ice-dammed lakes; type II floods are Glacial outburst floods from Canada, which occurred in the terminal

Pleistocene, after glaciers had receded north of the international boundary; type III floods are those from Glacial Lake Missoula, the largest of which formed the gravel plateau on which the 200 Areas are located. Craig and Hanson (1985) describe the erosion potential of Missoula Floods in the Pasco Basin, which would be the type most likely to be of concern for any long-term performance assessment.

As the globe recovered from the height of the last glacial period, temperatures started to warm very rapidly and in some quarters had reached temperatures very close to modern about 12,000 years ago. Throughout this time period glacial melt water ran down the Mississippi River. However, about 11,000 years ago, the Laurentide Ice Sheet had retreated far enough into Canada that the major drainage of glacial melt water was shifted from the Mississippi drainage to that of the Saint Lawrence River. As a result of this change in drainage, a large pulse of fresh water was injected into the North Atlantic. Because fresh water is lighter than salt water and has a higher freezing point, the fresh water remained at the surface without mixing and froze. This fresh-water sea ice spread across the North Atlantic, essentially putting a lid on the entire North Atlantic and effectively cutting off a critical source of heat from the ocean, and Europe and Eastern North America were thrown back into a short-lived ice age (termed the Younger Dryas in Europe) almost as severe as the one they had just come out of. As the continental ice continued to recede towards Hudson Bay, the amount of fresh water from the Saint Lawrence River was sharply curtailed and the fresh-water sea ice could not be sustained. The North Atlantic region then recovered from the Younger Dryas ice age.

The study of rapid change such as that which occurred with the Younger Dryas is important because it demonstrates how an earth born mechanism, the change in the route and amount of melt water, can drastically influence climate. The marine record of climatic change seems to show a progressive buildup of continental ice sheets from the previous interglacial through a glacial maximum. However, two recent studies in the Western United States suggest that the movement into and out of a glacial climate may be quite abrupt. Phillips et al. (1990a) presents repeated evidence for abrupt interglacial/glacial transition in the 1.4-million-year water balance record from Searles Lake, California. They indicate that the lengthy Searles Lake record can be precisely correlated with the marine record through radiometric dating. However, the Searles record, rather than showing a "sawtooth" pattern of glacial cycles characterized by gradually increasing ice volumes followed by very rapid ice volume decrease, shows lake surface area increases at the beginning of glaciations that are almost as rapid as the declines at the glacial terminations. They note that this may be a more accurate reflection of continental climate than the marine record, which may be controlled by the slow dynamics of continental ice sheet formation.

A second paper by Phillips et al. (1990b) reinforces the conclusions of the first. These workers see a rapid response of mountain glaciers to global climate changes as indicated by ^{36}Cl ages of the glacial moraines in the Sierra Nevada Mountains. They draw this conclusion because moraines as large as the ones produced shortly before 18,000 years ago are being dated by ^{36}Cl to 115,000 years ago, the time immediately following the last interglacial (oxygen isotope stage 5e). This glacial record suggests to the authors that the transition into an ice age may be quite rapid and small mountain glaciers are able to respond more quickly than the slow buildup of continental ice shown in the marine record.

Such studies suggest that global climate change driven by slow changes in orbital parameters may be nonlinear in nature with feedback mechanisms that push the system toward one state or the other, either glacial or nonglacial, and that transition from one state to the other may be quite rapid. These observations have important implications for bracketing potential future climate change and for long-term performance assessment. It has been over 10,000 years since the last full glacial, and in view of the past patterns that have been in place for at least the last 800,000 years we are due to move back into a glacial climate. How rapidly that will occur is a matter of debate and the impact of the anthropogenic trace gases that increase the greenhouse effect is now just beginning to be evaluated (see section B.7).

B.6 Greenhouse Theory of Climate Change

Human activity apparently is rivaling nature's ability to produce climatic change as judged by the potential impact of the increase of some gases in the atmosphere (Hansen et al. 1981; Schneider 1989). The current buildup of carbon dioxide, methane, and other gases from the use of fossil fuels may lead to the warming of the lower atmosphere through a process dubbed the "greenhouse effect." The greenhouse effect is not entirely bad. Without greenhouse gases to help blanket the earth and hold heat in, our globe would be 24°C colder. The concern is based on the apparent very rapid increase of carbon dioxide in the atmosphere since 1958 when measurements of carbon dioxide were started. Since 1958 carbon dioxide levels have increased 25% and if the levels continue to increase at that rate, the amount of carbon dioxide will double its concentration from the estimated pre-industrial level by sometime in the middle of next century. Complex computer models suggest that global temperature will also increase, with estimates ranging from 1.5°C to 4°C (Houghton et al. 1990).

To date there have been a number of computer model simulations that continue to refine these predictions. A new set of greenhouse gas emission scenarios has been produced by the Intergovernmental Panel on Climate Change (IPCC) (Wigley and Raper 1992) that take into account the effects of CO₂ fertilization, feedback from stratospheric ozone depletion, and the radiative effects of sulphate aerosols. These moderate the prediction of future climatic change produced by the original study (Houghton et al. 1990). The projected global mean temperature change is less severe but still far beyond the limits of natural variability.

B.7 Performance Assessment and Long-Term Future Climate Change

Any realistic long-term performance assessment for waste disposal at the Hanford Site should allow for the impact of climate change. For convenience, principal pathways of radionuclide transport that could be influenced by climate change can be grouped into three categories: 1) transport in groundwater that could be influenced by a change in recharge rates due to climatic change; 2) natural disruptive events (such as actual glacial scour, or catastrophic flood scour); and 3) the human intrusion pathway, which could conceivably be influenced by climate change. For example, the probability of intrusion from well

drilling activities may increase if precipitation decreases. Initiation of a new glacial cycle during the next few thousand years will certainly affect potential recharge through alteration of precipitation, evaporation, plant cover, and ultimately catastrophic flooding from the advance of continental ice to a position that would again block the large rivers in Washington.

Changes in recharge rates must take into account the potential local effect of greenhouse warming. Regional studies are still developing but good preliminary work is provided by Leovy and Sarachik (1991) and Franklin et al. (1991). Most of the models predict increased temperature (Houghton et al. 1990). The paleoclimate studies for eastern Washington discussed previously provide a valuable analog because temperatures were judged to be approximately 1°C to 2°C warmer 6,000 to 8,000 years ago than they are today, with slightly drier than current conditions. This provides a change in the right direction similar to that predicted to occur from the increases in atmospheric concentrations of greenhouse gases and the resulting increase in global temperatures of up to 3°C over the next 100 years (Houghton et al. 1990).

The models are not as consistent in their 100-year predictions of changes in precipitation from greenhouse warming (Houghton et al. 1990; Crowley and North 1991). The warmer atmosphere will have a greater capacity to hold more water. Globally, that may mean it will be wetter, but some regions are likely to be drier because of the greater evaporation potential.

In spite of the potential for future warming from the greenhouse effect, ultimately this effect will be overwhelmed as we plunge into the next ice age. Berger et al. (1991) review seven models of different complexity developed to predict the global climate for the next 10,000 to 100,000 years (e.g., Calder 1974; Petersen and Larsen 1978; Melice and Berger 1989; Imbrie and Imbrie 1980; Kukla et al. 1981; Berger 1981; Berger et al. 1990). All of the models are in relatively good agreement with the computation of astronomical forcing of climate change. In the absence of anthropogenic disturbances, the long-term cooling trend which began some 6,000 years ago will continue for the next 5,000 years; this first slight minimum will be followed by a stabilization at about 15,000 years, by a cold interval centered at approximately 25,000 years, and finally by a major glaciation at about 55,000 years. If, however, the Greenland ice sheet were to disappear in the next few centuries from the effects of greenhouse warming, for example, the northern hemisphere ice sheets would not reappear before 15,000 years from now; the climate would remain different from its natural evolution up to 65,000 years into the future, the maximum ice volume amounting to only two-thirds of its naturally expected size at that time.

Winograd et al. (1992) has questioned the regular cyclic timing used in part to date the pace of the ice ages (e.g., Berger et al. 1991, Hays et al. 1976) by using a well-dated and uninterrupted 500,000-year paleotemperature record contained in ¹⁸O concentrations in calcite deposits below the water table in a Nevada crevasse called Devils Hole. Rather than a steady beat of ice-age-and-interglacial lasting a combined 110,000 years, as predicted by celestial mechanics, Winograd et al. (1992) found that beginning 420,000 years ago the ice-age-and-interglacials had increasing lengths of 79,000, 85,000, 113,000, and finally 128,000 years providing an aperiodic swing to the climate cycle. The implication Winograd et al.

(1992) see for waste isolation is that the present interglacial may last another 10,000 years and continental glacial ice may not reach its maximum extent until 100,000 years into the future. This is important because of the relationship between continental glacial ice and the potential for catastrophic flooding.

B.8 References

Balling, R. C., Jr., and M. P. Lawson. 1982. "Twentieth Century Changes in Winter Climatic Regions." *Climatic Change*, 4:57-69.

Barnosky, C. W., P. M. Anderson, and P. J. Bartlein. 1987. "The Northwestern U.S. During Deglaciation; Vegetation History and Paleoclimatic Implications." In W. F. Ruddiman and H. E. Wright, Jr. (eds), *North America and Adjacent Oceans During the Last Deglaciation, The Geology of North America, Volume K-3*, Geological Society of America, Boulder, Colorado, pp. 289-321.

Berger, A. L. 1981. "The Astronomical Theory of Paleoclimates." In A. Berger (editor), *Climatic Variations and Variability: Facts and Theories*, D. Reidel Publishing Company, Dordrecht, Holland, pp. 501-525.

Berger, A., J. Imbrie, J. Hays, G. Kukla, and B. Saltzman (editors). 1984. *Milankovich and Climate*, D. Reidel, Dordrecht, Holland.

Berger, A., H. Galle, Th. Fichet, I. Marsiat, and C. Tricot. 1990. "Testing the Astronomical Theory with a Coupled Climate-Ice Sheet Model." *Palaeogeography, Palaeoclimatology, Palaeoecology* (Global and Planetary Change Section), 89:125-141.

Berger, A., H. Gallee, and J. L. Melice. 1991. "The Earth's Future Climate at the Astronomical Time-scale." In G. M. Goodess and J. P. Palutikof, *Future Climate Change and Radioactive Waste Disposal: Proceedings of International Workshop, NSS/R257*, U.K. Nirex Radioactive Waste Disposal, Ltd., Harwell, OX11 0RH, United Kingdom, pp. 148-165.

Berger, W. H., and L. D. Labeyrie (editors). 1987. *Abrupt Climatic Change: Evidence and Implications*, D. Reidel, Dordrecht, Holland.

Burhank, D. W. 1982. "Correlations of Climate, Mass Balances, and Glacial Fluctuations at Mount Rainier, Washington, U.S.A., Since 1850." *Arctic and Alpine Research*, 14(2):137-148.

Calder, N. 1974. "Arithmetic of Ice Ages." *Nature*, 252:216-218.

- Chatters, J. C. 1991. "Long-Term Climate Change Effects." In L.L. Cadwell (editor), Hanford Site Protective Barrier Development Program: Fiscal Year 1990 Highlights, PNL-7831, Pacific Northwest Laboratory, Richland, Washington, pp. 2.23-3.1.
- Chatters, J. C., D. A. Neitzel, M. J. Scott, and S. A. Shankle. 1991. "Potential Impacts of Global Climate Change on Pacific Northwest Spring Chinook Salmon (*Oncorhynchus tshawytscha*): An Exploratory Case Study." *The Northwest Environmental Journal*, 7:71-92.
- Chatters, J. C., and K. A. Hoover. 1992. Response of the Columbia River Fluvial System to Holocene Climatic Change." *Quaternary Research*, 37:42-59.
- Coatley, S. M. 1979. "Climate Variability in the Pacific Northwest and Its Effect on Stripe Rust Disease of Winter Wheat." *Climatic Change*, 2:33-51.
- COHMAP Members. 1988. "Climatic Changes of the Last 18,000 Years: Observations and Model Simulations." *Science*, 241:1043-52.
- Craig, R. G. and J. P. Hanson. 1985. *Erosion Potential from Missoula Floods in the Pasco Basin, Washington*. PNL-5684, Pacific Northwest Laboratory, Richland, Washington.
- Cropper, J. P. and H. C. Fritts. 1986. *A 360 Year Temperature and Precipitation Record for the Pasco Basin Derived from Tree Rings*. DOE-RL-01830- T46, U.S. Department of Energy, Richland, Washington.
- Crowley, T. J., and G. R. North. 1991. *Paleoclimatology*, Oxford Monographs on Geology and Geophysics No. 16, Oxford University Press, New York.
- Daubenmire, R. 1970. *Steppe Vegetation of Washington*, Washington Agricultural Experiment Station, Technical Bulletin 62, Pullman, Washington.
- DOE. 1987. *Final Environmental Impact Statement for the Disposal of Hanford Defense High-Level, Transuranic, and Tank Waste*, DOE/EIS-0113, U.S. Department of Energy, Richland Operations Office, Richland, Washington.
- Earth System Sciences Committee, NASA Advisory Council. 1988. *Earth System Science: A Closer View*, National Aeronautics and Space Administration, Washington, D.C.
- Franklin, J. F., F. J. Swanson, M. E. Harmon, D. A. Perry, T. A. Spies, V. H. Dale, A. McKee, W. K. Ferrell, J. E. Means, S. V. Gregory, J. D. Lattin, T. D. Schowalter, and D. Larsen. 1991. "Effects of Global Climatic Change on Forests in Northwestern North America." *The Northwest Environmental Journal*, 7:233-254.

- Fritts, H. C. 1976. *Tree Rings and Climate*, Academic Press, New York.
- Gramulich, L. J. 1987. "Precipitation Variation in the Pacific Northwest (1675-1975) as Reconstructed from Tree Rings." *Annals of the Association of American Geographers*, 77:19-29.
- Grazulis, T. P. 1984. *Violent Tornado Climatology, 1880-1982*, NUREG/CR-3670, Nuclear Regulatory Commission, Washington, D.C.
- Hansen, J., D. Johnson, A. Lacis, S. Lebedeff, P. Lee, D. Rind, and G. Russell. 1981. "Climate Impact of Increasing Atmospheric Carbon Dioxide." *Science*, 213:957-966.
- Hays, J. D., J. Imbrie, and N. J. Shackleton. 1976. "Variations in the Earth's Orbit: Pacemakers of the Ice Ages." *Science*, 194:1121-1132.
- Heermann, D. F., M. D. Finkner, and E. A. Hiler. 1971. *Probability of Sequences of Wet and Dry Days for Eleven Western States and Texas*, Colorado State University Experiment Station, Technical Bulletin 117, Fort Collins, Colorado.
- Houghton, J. T., G. J. Jenkins, and J. J. Ephraums. 1990. *Climate Change: The IPCC Scientific Assessment*, Cambridge University Press, Cambridge, United Kingdom.
- Imbrie, J., and J. Z. Imbrie. 1980. "Modeling the Climatic Response to Orbital Variations." *Science*, 207:943-953.
- Kukla, G. J. 1981. "Pleistocene Climates on Land." In A. Berger (editor), *Climate Variations and Variability: Facts and Theories*, D. Reidel Publishing Company, Dordrecht, Holland, pp. 207-232.
- Kukla, G., A. Berger, R. Lotti, and J. P. Brown. 1981. "Orbital Signature of Interglacials." *Nature*, 290:295-300.
- Leovy, C. and E. S. Sarachik. 1991. "Predicting Climate Change for the Pacific Northwest." *The Northwest Environmental Journal*, 7:169-201.
- Manabe, S. and A. J. Broccoli. 1985. "The Influence of Continental Ice Sheets on the Climate of An Ice Age." *Journal of Geophysical Research*, 90:2167-90.
- Melice, J. L., and A. Berger. 1989. "Modele de prevision statistique du type Box-Jenkins pour la prevision du climat des 10,000 prochaines annees." Scientific Report 1989/6, Institut d'Astronomie et de Geophysique G. Lemaître, Université Catholique de Louvain-la-Neuve, Belgium.

- Mitchell, J. M., Jr. 1987. "Climatic Variation, Instrumental Data." In J. E. Oliver and R. W. Fairbridge (editors), *The Encyclopedia of Climatology*, Van Nostrand Reinhold, New York, pp. 323-327.
- Petersen, E. L. and S. E. Larsen. 1978. "A Statistical Study of a Composite Isotopic Paleotemperature Series from the Last 700,000 Years." *Tellus*, 30:193-200.
- Petersen, K. L., J. C. Chatters, and W. J. Waugh. 1992. *Long-Term Climate Change Assessment Study Plan for the Hanford Site Permanent Isolation Barrier Development Program*. WHC-EP-0569, Westinghouse Hanford Company, Richland, Washington.
- Phillips, F. M., A. C. Campbell, R. Roberts, and C. V. Kruger. 1990a. "Abrupt Interglacial/Glacial Transition in the 1.4 Ma Waterbalance Record from Searles Lake, California." In American Quaternary Association Program and Abstracts, June 4-6, 1990, University of Waterloo, Waterloo, Ontario, pp. 28.
- Phillips, F. M., M. G. Zreda, S. S. Smith, D. Elmore, P. W. Kubik, and P. Sharma. 1990b. "Cosmogenic Chlorine-36 Chronology for Glacial Deposits at Bloody Canyon, Eastern Sierra Nevada." *Science*, 248:1529-32.
- Quinn, R. L. 1977. *The Late Spring Secondary Precipitation Maximum in the Interior Pacific Northwest*, Ph.D. Dissertation, Department of Geography, Oregon State University, University Microfilms International, Ann Arbor, Michigan.
- Ramsdell, J. V., and G. L. Andrews. 1986. *Tornado Climatology of the Contiguous United States*. NUREG/CR4461, Nuclear Regulatory Commission, Washington, D.C.
- Risser, P. G., E. C. Birney, H. D. Blocker, S. W. May, W. J. Parton, and J. A. Weins. 1981. *The True Prairie Ecosystem*, Hutchinson Ross Publishing Company, Stroudsburg, Pennsylvania.
- Ruffner, J. A. and F. E. Bair (editors). 1977. *The Weather Almanac*, 2nd edition, Gale Research Company, Book Tower, Detroit, Michigan.
- Schneider, S. H. 1989. *Global Warming*, Sierra Club Books, San Francisco, California.
- Stone, W. A., J. M. Thorp, O. P. Gifford, and D. J. Houtink. 1983. *Climatological Summary for the Hanford Area*. PNL-4622, Pacific Northwest Laboratory, Richland, Washington.
- Wigley, T. M. L., and S. C. B. Raper. 1992. "Implications for Climate and Sea Level of Revised IPCC Emissions Scenarios." *Nature*, 357:293-300.

Winograd, I. J., T. B. Coplen, J. M. Landwehr, A. C. Riggs, K. R. Ludwig, B. J. Szabo, T. P. Kolesar, and M. Revesz. 1992. "Continuous 500,000-Year Climate Record from Vein Calcite in Devils Hole, Nevada." *Science*, 258:255-260.

Appendix C

Geology and Aquifer Characteristics of the Grout Treatment Facility^(a)

-
- (a) This appendix is a reproduction of document number WHC-SD-EN-TI-071, Rev. 0, prepared by Westinghouse Hanford Company. (J. W. Lindberg, J. V. Borghese, B. N. Bjornstad, and M. P. Connelly. 1993. *Geology and Aquifer Characteristics of the Grout Treatment Facility*. WHC-SD-EN-TI-071, Rev. 0. Westinghouse Hanford Company, Richland, Washington.)

SUPPORTING DOCUMENT

1. Total Pages 37

2. Title

Geology and Aquifer Characteristics of the Grout Treatment Facility

3. Number

WHC-SD-EN-TI-071

4. Rev No.

0

5. Key Words

Hanford formation, Ringold Formation, basalt, Ringold lower mud unit, Ringold gravel unit A, Ringold gravel unit E, Hanford upper gravel sequence, Hanford middle sandy sequence, Hanford lower gravel sequence, uppermost aquifer system, transmissivity, hydraulic conductivity, groundwater flow, vertical gradients, hydraulic properties

6. Author

Name: JW Lindberg
JV Borghese
BN Bjornstad
MP Connelly

Signature

1/19/93
Organization/Charge Code
81231/D44HB

APPROVED FOR
PUBLIC RELEASE
1-18-93 N.S.W.

7. Abstract

WHC, 1992, *Geology and Aquifer Characteristics of the Grout Treatment Facility*, WHC-SD-EN-TI-071, Rev. 0, prepared by J. W. Lindberg and M. P. Connelly, Westinghouse Hanford Company, Richland, Washington, and J. V. Borghese and B. N. Bjornstad, Pacific Northwest Laboratory, Richland, Washington.

The geology and aquifer characteristics of the area at the Grout Treatment Facility is interpreted and described in support of the Performance Assessment of the Grout Treatment Facility. The study used the most currently available geologic and hydrologic data. A comprehensive set of isopach and structure contour maps is developed for each geologic unit in the area, and geologic cross sections are provided. Groundwater flow, vertical gradients, and hydraulic properties of the uppermost aquifer system are discussed.

8. ~~PURPOSE AND USE OF DOCUMENT - This document was prepared for use within the U.S. Department of Energy and its contractors. It is to be used only to perform, direct, or integrate work under U.S. Department of Energy contracts. This document is not approved for public release until reviewed.~~

~~PATENT STATUS - This document is not, since it is transmitted in advance of patent clearance, is made available in confidence solely for use in performance of work under contracts with the U.S. Department of Energy. This document is not to be published nor its contents otherwise disseminated or used for purposes other than specified above before patent approval for such release or use has been secured, upon request, from the Patent Counsel, U.S. Department of Energy Field Office, Richland, WA.~~

DISCLAIMER - This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

10.

RELEASE STAMP

OFFICIAL RELEASE (11)
BY WHC

DATE JAN 21 1993

Station # 12

9. Impact Level 4

CONTENTS

1.0	GEOLOGY OF THE GROUT TREATMENT FACILITY	1
1.1	BASALT AND INTERBED GEOLOGY AND GEOLOGIC STRUCTURE	1
1.2	RINGOLD FORMATION	8
1.2.1	Unit A of the Ringold Formation	8
1.2.2	Lower Mud Unit of the Ringold Formation	8
1.2.3	Unit E of the Ringold Formation	8
1.2.4	Upper Surface of the Ringold Formation	13
1.3	PLIO-PLEISTOCENE UNIT AND EARLY "PALOUSE" SOIL	13
1.4	HANFORD FORMATION	13
1.4.1	Lower Gravel Sequence	17
1.4.2	Sandy Sequence	17
1.4.3	Upper Gravel Sequence	22
1.4.4	Total Hanford Formation	22
1.4.5	Clastic Dikes	22
1.5	HOLOCENE SURFICIAL DEPOSITS	25
2.0	HYDROLOGY OF THE UPPERMOST AQUIFER SYSTEM	25
2.1	UPPERMOST AQUIFER SYSTEM	26
2.2	GROUNDWATER FLOW	29
2.3	VERTICAL GRADIENTS	29
3.0	REFERENCES	32

LIST OF FIGURES

1	Grout Treatment Facility Location Map	2
2	Geologic Cross Section A-A', Grout Treatment Facility	3
3	Geologic Cross Section B-B', Grout Treatment Facility	4
4	General Stratigraphy of the Hanford Site	5
5	Structure Contour Map Top of Basalt	7
6	Isopach Map Ringold Formation Gravel Unit A	9
7	Structure Contour Map Ringold Formation Gravel Unit A	10
8	Isopach Map Ringold Formation Lower Mud Unit	11
9	Structure Contour Map Ringold Formation Lower Mud Unit	12
10	Isopach Map Ringold Formation Gravel Unit E	14
11	Structure Contour Map Ringold Formation Unit E	15
12	Geologic and Structure Countour Map Top of Ringold Formation	16
13	Isopach Map Hanford Formation Lower Gravel Sequence	18
14	Structure Contour Map Hanford Formation Lower Gravel Sequence	19
15	Isopach Map Hanford Formation Sandy Sequence	20
16	Structure Contour Map Hanford Formation Sandy Sequence	21
17	Isopach Map Hanford Formation Upper Gravel Sequence	23
18	Isopach Map of the Hanford Formation (total thickness)	24
19	Isopach Map of the Uppermost Aquifer System	27
20	Geologic Map of the Water Table	28
21	Potentiometric Surface Map for the Upper Part of the Uppermost Aquifer System in the Area of the 216-B-3 Pond System and Grout Treatment Facility	30

LIST OF TABLES

1	Transmissivity and Hydraulic Conductivity Values for the Upper Uppermost Aquifer	31
---	--	----

1.0 GEOLOGY OF THE GROUT TREATMENT FACILITY

The geology in the vicinity of the Grout Treatment Facility (GTF) has been discussed in previous reports on the geology and hydrogeology of the 200 East Area for the CERCLA Aggregate Area Management Study (Lindsey et al. 1992; WHC 1992). The following discussion is based on the geologic discussions in those reports but focuses on the GTF. Additional information on Hanford Site geology can be found in Delaney et al. (1991), Myers et al. (1979), and DOE (1988).

This report is based on geologic data derived largely from wells in the vicinity of the GTF. The location of these wells is shown in Figure 1 (the "map area")¹. The map also shows the boundary locations of the 200 East Area and the GTF, the 216-B-3 Pond System (B-Pond), and the locations of the geologic cross sections A-A' (Figure 2) and B-B' (Figure 3).

Flows of the Columbia River Basalt Group form the bedrock beneath the GTF. These basalt flows are overlain by the Ringold Formation, which in turn overlain by the Hanford formation (Figure 4). A discontinuous veneer of Holocene eolian sand overlies the Hanford formation.

1.1 BASALT AND INTERBED GEOLOGY AND GEOLOGIC STRUCTURE

The uppermost basalt flows beneath the GTF belong to the Elephant Mountain Member of the Saddle Mountains Basalt which, in turn, is part of the Columbia River Basalt Group (Reidel and Fecht 1981). The Elephant Mountain Member locally contains two basalt flows: the Ward Gap (upper) and Elephant Mountain (lower) flows. The Elephant Mountain flow is continuous throughout the map area. However, the Ward Gap flow, which is present to the southeast, pinches out or terminates to the northwest approximately in the vicinity of the GTF (Graham et al. 1984). The exact position of the termination of the Ward Gap flow is unknown. In the area of the GTF the Elephant Mountain Member is approximately 25 m to 30 m thick.

The Elephant Mountain Member is underlain by the Rattlesnake Ridge interbed of the Ellensburg Formation. Typical sediments in the Rattlesnake Ridge interbed are a lower clay or tuffaceous sandstone, a middle micaceous-arkosic and/or tuffaceous sandstone, and an upper tuffaceous siltstone or sandstone. In the vicinity of the GTF, the Rattlesnake Ridge interbed is about 20 m thick.

The Pomona Member of the Saddle Mountains Basalt lies beneath the Rattlesnake Ridge interbed. In the vicinity of the 200 East Area, the Pomona member is about 50 m to 55 m thick.

¹The "map area" is the area in the immediate vicinity of the Grout Treatment Facility. Specifically, it is the area shown in Figure 1 and Figures 5 through 18 (all these maps cover exactly the same area). The "GTF area" (or the area of the GTF) is the area within the boundary of the GTF.

Figure 1. Grout Treatment Facility Location Map.

Legend:

2-E26-13 Well Location

Location of geologic cross section

0 200 400 Meters

Figure 2. Geologic Cross Section A-A', Grout Treatment Facility.

Figure 3. Geologic Cross Section B-B', Grout Treatment Facility.

Figure 4. General Stratigraphy of the Hanford Site.

H9112007.1

The GTF is situated on the generally south-dipping limb of the Gable Mountain anticline. The Gable Mountain anticline consists of a series of *en echelon*, southeast-northwest-trending folds (Fecht 1978). The main axis lies about 6 km north-northeast of the GTF. Two *en echelon* folds similar to (but smaller than) Gable Mountain occur outside of the map area on the south limb of the anticline between the main axis and the GTF. One of these subsidiary anticlines lies about 3 km north-northwest of the GTF, and another lies approximately 2.4 km to the northwest of the GTF. Both subsidiary anticlines trend northwest-southeast and have been uplifted high enough that basalt is above the current water table.

South of these two subsidiary anticlines, basalt flows, sedimentary interbeds, and Ringold Formation dip southward into the Cold Creek syncline. This southward dip is apparent on a structure contour map² of the upper basalt surface (Figure 5). The upper basalt surface dips southward approximately 28 m per km.

²All contour maps in this report were generated by Interactive Surface Modeling (ISM™) from Dynamic Graphics, Inc. on a Silicon Graphics Personal Iris™ engineering workstation. This program uses a bi-harmonic cubic spline to fit a surface through the data points. The isopach maps and structure contour maps were built by generating the top-of-basalt map and then working upward. Each succeeding layer must account for the layers beneath it. Finally, the uppermost layer must be consistent with the ground surface. Therefore, at times the reader will note that there seems to be more detail than the data suggest. This extra detail is from information that was passed from the layers below.

There are both advantages and disadvantages to computerized contouring. The major advantages are ease of contouring, the ability to manipulate the contour maps after generating them, and having a consistent contour method in order to compare changes from map to map. The major disadvantages are poor extrapolation in areas with little or no data, bulls-eyes around inconsistent data points, and extra contour lines with little or no data to explain the contour line. Generally, the advantages outweigh the disadvantages. However, it should be remembered that two-dimensional maps (showing the general trend and values between boreholes) created from one-dimensional borehole data are an approximation at best.

In the contour maps presented in this report, there was an attempt to use all available data. However, only the actual borehole data relating to the particular surface or layer are shown on the maps. For example, if a borehole did not fully penetrate a geologic layer (unit, sequence, formation), an interpolated thickness value was calculated. This thickness value was calculated by subtracting the elevation on the overlying structure contour map from the elevation on the underlying structure contour map. However, at that position on the map a value would not be printed. In contrast, when a borehole fully penetrates a geologic layer, the data derived from that borehole would be printed on the map.

Additionally, control points were used to control the extrapolation in areas where there are few data points. These control points are based on the geologist's knowledge of how these units were trending outside the boundaries used on these maps.

Figure 5. Structure Contour Map Top of Basalt.

Legend:

- Well Location (no data)
- Well Location with elevation (in meters)
88.7 of top of basalt
- 50— Contour of the upper
surface of basalt (in meters)
- Contour Interval = 5m

0 200 400 Meters

1.2 RINGOLD FORMATION

Ringold Formation strata are found throughout the GTF and vicinity where they overlie basalt. The relationship between the Ringold Formation and the underlying basalt varies between a disconformity and a low-angle unconformity. Strata within the Ringold Formation are divided, from the bottom to the top, into fluvial gravels of unit A, the paleosol and lacustrine muds of the lower mud unit, and the fluvial gravels of unit E (Lindsey et al. 1992). Fluvial units B and D are not present near the GTF, and fluvial unit C and the overbank-dominated deposits of the upper Ringold unit are encountered only at borehole 6-37-43 in the southern portion of the area (Figure 1). Immediately northwest of borehole 6-37-43, fluvial unit C and the upper Ringold unit pinch out. South of borehole 6-37-43, both units thicken into the Cold Creek syncline.

1.2.1 Unit A of the Ringold Formation

The fluvial gravels and intercalated sands of unit A are located throughout the entire map area and generally thicken from less than 10 m near the northern end of the map area to over 40 m near the southern boundary of the GTF (Figure 6). South of the GTF, unit A decreases in thickness to less than 25 m near the southern boundary of the map area. The upper surface of unit A is relatively flat in the northern one-third of the map area, but dips southward in the southern two-thirds (Figure 7). The GTF is located mostly in the northern portion that is relatively flat. This relatively flat area is the portion of unit A locally that was exposed and beveled by Pleistocene cataclysmic flooding. To the south, the unit dips beneath younger Ringold Formation units that protected it from the scouring action of the cataclysmic flooding.

1.2.2 Lower Mud Unit of the Ringold Formation

The overbank and lacustrine deposits of the lower mud unit overlie unit A in the southern and eastern portions of the map area and generally thicken and dip to the south (Figures 8 and 9). The lower mud unit is generally absent within, north of, and west of the GTF. The thickness of the lower mud unit ranges from zero to over 25 m (in the southeastern portion of the map area). None of the wells within the boundary of the GTF encountered the lower mud unit. Therefore, the position of the pinchout of the lower mud unit is unknown. The zero thickness line is irregular and probably runs around the southern portion of the GTF and then northward through B-Pond. The pinchout is due to truncation by overlying deposits of Ringold Formation unit E or Hanford formation.

1.2.3 Unit E of the Ringold Formation

Unit E, the uppermost unit of the Ringold Formation in the vicinity of the GTF, is not found within the boundaries of the GTF. It is composed dominantly of fluvial gravel, but strata typical of the fluvial sand and overbank facies (mud) may be encountered locally. Predicting where intercalated lithologies occur is very difficult. The zero thickness line

Figure 6. Isopach Map Ringold Formation Gravel Unit A.

JWL\081092-K

Legend:

- Well Location (no data)
- Well Location with Unit A thickness (in meters)
- 13.7
- 35 — Isopach of thickness of Ringold Formation Gravel Unit A (in meters)
- Contour Interval = 2.5m

0 200 400 Meters

Figure 7. Structure Contour Map Ringold Formation Gravel Unit A.

Figure 8. Isopach Map Ringold Formation Lower Mud unit.

Legend:

- Well Location (no date)
 - Well Location with Lower Mud Unit (in meters)
 - Well Location where Lower Mud Unit is not present
 - 0— Isopach of thickness of Lower Mud Unit (in meters)
- Contour interval = 2.5m

Figure 9. Structure Contour Map Ringold Formation Lower Mud Unit.

Legend:

- Well Location with data
- Well Location, Lower Mud Unit not present
- 115— Contour on upper surface of Lower Mud Unit (in meters)
- Contour interval = 2.5m

0 200 400 Meters

crosses the map area in an approximate east-west direction south of the GTF (Figure 10). The unit generally thickens to the south and somewhat to the west. The unit is thickest in the southwestern portion of the map area (>40 m). The unit generally dips to the north (Figure 11), and its upper surface is very irregular due to scouring by Pleistocene cataclysmic flooding.

1.2.4 Upper Surface of the Ringold Formation

The top of the Ringold Formation consists of Ringold Formation unit A in the northern and central portions of the map area, the Ringold Formation lower mud unit in the east-central portion of the map area, and Ringold Formation unit E in the southern portion of the map area (Figure 12). This surface (which also represents the base of the Hanford formation) is an irregular surface that generally slopes to a local depression in the surface immediately south of the GTF. The surface ranges in elevation from less than 110 m in the local depression to over 130 m to the northwest and southwest (Figure 12).

During and subsequent to the deposition of the Ringold Formation, the uplift of the Gable Mountain anticline tilted Ringold Formation strata in the map area so that the beds dip southward into the Cold Creek syncline (Section 1.1). This uplift positioned the Ringold Formation strata such that subsequent Pleistocene-aged cataclysmic flooding scoured the up-turned ends of the Ringold Formation strata. Cataclysmic flood erosion peeled back the upper layers of the Ringold Formation in the northern portion of the map area exposing the lower mud unit and unit A (Figure 12) and produced the northwest-southeast channel system that is present throughout the map area.

1.3 PLIO-PLEISTOCENE UNIT AND EARLY "PALOUSE" SOIL

The Plio-Pleistocene unit and early "Palouse" soil are not found in or near the GTF. They either never developed in this area or were eroded away during cataclysmic flooding. The closest occurrence of these sediments is near the eastern boundary of the 200 West Area (Last et al. 1989; DOE 1988; and Lindsey et al. 1991).

1.4 HANFORD FORMATION

The Hanford formation (informal designation) is continuous over the entire GTF area and vicinity. Figure 12, besides being a geologic map of the top of the Ringold Formation, is a structure contour map of the bottom surface of the Hanford formation. From this map it can be seen that the surface upon which the Hanford formation was deposited is irregular but overall has low relief. This relatively horizontal area is a portion of a large channel sequence that extends southeastward from Gable Gap (northwest of the map area). The channel sequence is identified by eroded and missing Ringold Formation strata and the character of Hanford formation sediments deposited in this area. The channeling and the characteristic Hanford formation sediments are the result of Pleistocene-age cataclysmic flooding that was (in part) directed by the underlying basalt structure (parasitic folds with the same trend).

Figure 10. Isopach Map Ringold Formation Gravel Unit E.

Legend:

- Well Location (no data)
- Well Location with Unit E thickness (in meters)
- Well Location where Unit E is not present
- C— Isopach of thickness of Unit E (in meters)
- Contour Interval = 5m

Figure 11. Structure Contour Map Ringold Formation Unit E.

Legend:

- Well Location (no data)
- Well Location with Unit E data
- Well Location where Unit E not present
- 20 — Contour on upper surface of Gravel Unit E (in meters)
Contour interval = 5m

Figure 12. Geologic and Structure Countour Map Top of Ringold Formation.

Legend:

Ringold Formation
Gravel Unit E Ringold Formation
Lower Mud Unit Ringold Formation
Gravel Unit A

-50-

Contour on upper surface
of Ringold Formation (in meters)

Contour interval = 5m

0 200 400 Meters

As discussed in Lindsey et al. (1992), the cataclysmic flood deposits of the Hanford formation are divided into three facies: gravel-dominated, sand-dominated, and silt-dominated. Based on the distribution of these three facies, the Hanford formation is tentatively divided locally into three informal lithostratigraphic sequences. Starting from the bottom, these sequences are designated as follows: (1) lower gravel, (2) sandy, and (3) upper gravel sequences. However, because of the variability of Hanford formation sediments, contacts between these sequences are sometimes difficult to distinguish. Furthermore, these lithostratigraphic sequences are not time-stratigraphic sequences. For example, the lower gravel sequence locally may be time equivalent to the sandy sequence in another location because during one cataclysmic flood event both gravel and sand were deposited at the same time. Gravel was deposited with main channel areas, and sand was deposited toward the margins of channels. The three Hanford formation sequences discussed here are essentially the same strata as identified in Last et al. (1989).

1.4.1 Lower Gravel Sequence

The lower gravel sequence is dominated by deposits typical of the gravel-dominated facies. Local intercalated sandy beds typical of the sand-dominated facies are also found, and some minor beds of silt are found in the southern portion of the map area. The lower gravel sequence is missing in the western and northwestern portions of the map area but thickens to over 40 m in the north-central portion of the map area (Figure 13). In the GTF the thickness ranges from about 10 to 30 m. The upper surface is generally higher in areas where the sequence is thickest and slopes downward toward the pinchout (zero thickness line) to the northwest (Figure 14). The contact between the sandy and lower gravel sequences is placed at the top of the first thick gravelly interval (6 m or greater in thickness) encountered below the sand-dominated strata of the sandy sequence. This contact may not be at the same horizon at all localities because of local facies variability.

1.4.2 Sandy Sequence

The sandy sequence consists of a heterogeneous mix of deposits typical of the sand-dominated facies with minor amounts of sediments typical of the silt- and sand-dominated facies. The sandy sequence is differentiated from the overlying upper gravel sequence (where present) on the basis of the relative abundance of sand-dominated versus gravel-dominated deposits. The top of the sandy sequence is placed at the top of the highest thick (>6 m) sand-dominated interval. Although this sequence is composed predominantly of sand, gravel becomes more common toward the north (closer to main flood channels), and silt becomes more common to the south. Thickness of the sandy sequence ranges from less than 30 m northward and eastward of the map area to over 80 m in the western portion of the map area (Figure 15). The upper surface of the sandy sequence generally rises to the southwest (Figure 16), and this rise corresponds roughly with a general thickening of the sequence in the same direction. The sandy sequence may be laterally equivalent with the lower fine sequence in the 200 West Area (Last et al. 1989; Lindsey et al. 1991). The increase in thickness to the southwest also reflects a depositional environment with decreasing flood velocities away from the major flood

Figure 13. Isopach Map Hanford Formation Lower Gravel Sequence.

JNL\081092-C

Legend:

- Well Location (no data)
 - Well Location with thickness data (in meters)
 - Well Location where lower gravel sequence is missing
 - 0— Isopach of thickness of lower gravel sequence (in meters)
- Contour Interval = 5m

Figure 14. Structure Contour Map Hanford Formation Lower Gravel Sequence.

Legend:

- Well Location (no data)
- Well Location with elevation (in meters)
150.8 of top of basalt
- Well Location where the
lower gravel sequence is not present
- 150— Contour on upper surface of the
lower gravel sequence (in meters)
- Contour interval = 5m

0 200 400 Meters

Figure 15. Isopach Map Hanford Formation Sandy Sequence.

JWL\041092-2

Legend:

- Well Location (no data)
- 55.17 Well location with thickness data (in meters)
- 56— top of sandy sequence (in meters)

Contour interval = 5m

0 200 400 Meters

Figure 16. Structure Contour Map Hanford Formation Sandy Sequence.

JWL\081092-F

Legend:

- Well Location (no data)
 - Well Location with elevation (in meters)
of top of basalt
 - 170— Contour on upper surface of the
sandy sequence (in meters)
- Contour Interval = 5m

0 200 400 Meters

channels to the northeast. The great thickness of sandy sequence with corresponding rise in the upper contact of the sequence is responsible for most of the flood bar that forms the eastern end of the 200 Areas plateau.

1.4.3 Upper Gravel Sequence

The uppermost deposits of the Hanford formation in the vicinity of the 200 East Area consist of gravel-dominated strata with lesser occurrences of the sand-dominated facies locally. This gravel-dominated sequence, identified as the upper gravel sequence in Lindsey et al. (1992), is missing over much of the area of the GTF (Figure 17). However, it does occur in all areas around the GTF. It is thickest to the northwest and southeast.

1.4.4 Total Hanford Formation

Figure 18 is an isopach map³ of the total Hanford formation including lower gravel, middle sandy, and upper gravel sequences. The overall thickness of Hanford formation in the GTF ranges from approximately 60 m in the northeast to almost 100 m in the southeast and southwest. However, in the map area, thickness ranges from less than 50 m near B-Pond to over 100 m in the area south of the GTF.

1.4.5 Clastic Dikes

Clastic dikes occur in the Hanford formation in the 200 East Area and vicinity. Several were found in the first excavation of the GTF. They are potentially important because, as discontinuities to the normal sedimentary bedding, they may affect the way groundwater (and contaminants) move in the vadose and saturated zones. Their age is probably Pleistocene, because they do not occur in Holocene eolian deposits and are sometimes truncated by Hanford formation sediments. It is not known whether clastic dikes occur in the Ringold Formation in the map area because they are difficult to identify in drill core, and excavations in the area do not reach the Ringold Formation. They do occur in Ringold Formation sediments elsewhere (Grolier and Bingham 1978), but these occurrences are rare. Total depth of the dikes is also unknown, but they extend over 30 m in the Touchet beds of the Walla Walla River valley (Alwin 1970). Some extend below the bottom of the excavation at the GTF. Where clastic dikes occur elsewhere at the Hanford Site they are often quite abundant and may form polygonal networks where they intersect the ground surface. Newcomb (1962) measured networks of clastic dikes and found they have cell diameters ranging from 15 m to 120 m.

³The isopach map of the total thickness of the Hanford formation is a computer generated map that was made by summing the isopach maps of the three sequences within the Hanford formation. The well locations and thickness values at each well location are not printed. Figures A-13, A-15, and A-17 show the contributions of each sequence and the locations of the wells.

Figure 17. Isopach Map Hanford Formation Upper Gravel Sequence.

JNL\081092-C

Legend:

- Well Location (no data)
- Well Location with thickness data (in meters)
- Well Location where upper gravel sequence is not present
- 20— isopach of thickness of upper gravel sequence (in meters)
- Contour Interval = 2.5m

Figure 18. Isopach Map of the Hanford Formation (total thickness).

JWL\081092-R

Legend:
 —50— Isopach of thickness of the
 total Hanford Formation (in meters)
 Contour Interval = 5m

0 200 400 Meters

Clastic dikes are found in all facies of the Hanford formation in the 200 East Area and the GTF, but they are most common in the silt- and sand-dominated facies and rare in gravel-dominated facies. Widths of the clastic dikes range from only a few centimeters to over a meter. Attitudes of the dikes range from vertical to horizontal, with near vertical dikes more common. Material filling the dikes is locally derived and ranges from mud to gravel. Clay, silt, and sand are most common. In some cases, filling material can be traced to underlying, overlying, or interbedded sediments. The dikes are either simple and composed of one layer of filling material, or composite and composed of multiple layers. Sometimes there is a fine layer of clay on dike walls.

Origin of clastic dikes in the Columbia Plateau has been attributed to earthquakes (Jenkins 1925), structural deformation (Flint 1938), melting of buried ice and frozen sediments (Lupher 1944), upward injections of groundwater (Newcomb 1962), thermal contraction of permafrost (Alwin 1970), desiccation cracks or deep frost cracks (Alwin 1970), and extension fracturing from the loading of flood deposits on unstable underlying sediments (Baker-1973). None of these suggested origins can explain all the characteristics displayed by the clastic dikes. They may actually be multigenetic. One mechanism proposed by Black (1979) accommodates most of the characteristics of dikes in the 200 East Area and GTF. He suggests that the dikes were formed during Pleistocene cataclysmic flooding and are the result of hydraulic injection of water and sediment into cracks formed by the sudden loading of water on the ground surface.

1.5 HOLOCENE SURFICIAL DEPOSITS

Holocene-aged deposits in the map area are dominated by eolian sheet sands. These deposits consist of very fine- to medium-grained sand to silty sand. The eolian deposits have been removed from much of the area by construction activities. Where the eolian sands are present they are in thin sheets, usually less than 3 m thick. The Holocene surficial deposits are not differentiated from the upper gravel sequence of the Hanford formation because they are relatively thin and because of the lack of definition on many of the borehole geologic logs available for the 200 East Area and vicinity. The eolian sands are generally stable when covered with natural vegetation. However, when this natural cover is disturbed the silty sand may be blown about by the wind.

2.0 HYDROLOGY OF THE UPPERMOST AQUIFER SYSTEM

The permeable saturated zone within the Hanford Site has been given a variety of names, including the suprabasalt aquifer, unconfined aquifer, semiconfined aquifer, uppermost aquifer, Ringold/Hanford producing layer, and Ringold confined aquifer. None of these names truly fits the aquifer system within the GTF and vicinity (the map area) or the Hanford Site. Delaney et al. (1991), in an attempt to avoid confusion and to standardize Hanford Site hydrogeologic terms, suggested the use of "the uppermost aquifer system"

rather than the unconfined aquifer. This report will use the term "uppermost aquifer system" for the suprabasalt saturated zone in the map area.

A conceptual model of the uppermost aquifer system for the 200 East Aggregate Area is presented in WHC (1992). Much of the information presented in this report is gleaned from the WHC 1992 report. The following sections describe the hydrologic characteristics of the uppermost aquifer system within the map area.

2.1 UPPERMOST AQUIFER SYSTEM

The uppermost aquifer system within the map area is defined as the saturated units above the uppermost basalt. The permeable portion of the uppermost aquifer system consists of the lower gravel of the Hanford formation and Ringold units A and E (fluvial gravel units). Where present, the lower mud of the Ringold Formation acts as a confining layer to Ringold unit A. The base of the uppermost aquifer system is the Elephant Mountain Member of the Saddle Mountain Basalt.

The uppermost aquifer system thickens to the south within the map area (Figure 19). The map was constructed by taking the difference in elevation between the water table and the top of basalt. The map indicates that the aquifer is about 20 m thick in the north of the map area and 50 m in the south.

The top of the uppermost aquifer system within the study area is contained within either Ringold unit A, E, the Hanford formation lower gravel sequence (or undifferentiated Hanford formation gravel) or the Hanford sandy sequence. Figure 20 shows the geologic units that the water table intersects. Within the western portion of the GTF the water table is contained within the Ringold unit A. The water table occurs within the Hanford formation lower gravel sequence (or undifferentiated Hanford formation gravel) in the eastern portion of the map area. In the western portion of the map area the water table occurs within the Ringold gravel units A and E and the Hanford sandy sequence.

The upper part of the uppermost aquifer system is under unconfined hydraulic conditions throughout the majority of the map area. However, information obtained from drilling and completion of groundwater monitoring wells near B-pond indicate unconfined conditions are absent in the southeastern part of B-Pond. Graham et al. (1984) noted that the lower mud (Ringold Formation lower mud unit) acts as an aquitard in the southwest portion of the 200 East Area. Davis and Delaney (1992) have stated that in the B-Pond area the lower mud unit also appears to act as a confining unit to the Ringold Unit A. Where the Ringold Formation lower mud unit is present above unit A, as it is within the map area, unit A is considered to be a semi-confined aquifer. Figures 7 and 9 show the extent of unit A and the lower mud unit of the Ringold Formation, respectively. The lower mud unit pinches out to the west of B-Pond and thickens to the southeast (Figure 8; Davis and Delaney 1992).

Figure 19. Isopach Map of the Uppermost Aquifer System.

Figure 20. Geologic Map of the Water Table.

- Hanford Gravels*
- Hanford Sand Sequence
- Ringold Gravel Unit E
- Ringold Lower Mud Unit
- Ringold Gravel Unit A

Facilities

- B Pond
- Grout Treatment Facility

* This includes upper, lower, and undifferentiated Hanford Gravels

H9209014.1

2.2 GROUNDWATER FLOW

The direction of the regional groundwater flow for the uppermost aquifer system within the study area is inferred from the Hanford Site Water Table Map and the 200 Areas Water Table Elevation map presented in Kasza et al. (1992). In general, regional flow is from west to east.

The regional flow system has been influenced by artificial recharge within the map area. Newcomer (1990) reports the major influence on the configuration of the water table in the map area is the B-Pond mound. The B-Pond mound has caused a higher water table elevation in the eastern portion of the 200 East Area. The B-Pond mound is declining at present (Newcomer 1990; DOE-RL 1992). Groundwater flow is from west to east in the area between the 200 East and West Areas, radially outward from B-Pond, and generally to the north between Gable Mountain and Gable Butte in the area north of the 200 East Area.

The direction of groundwater flow in the uppermost aquifer system within the map area away from the B-Pond mound historically has been difficult to determine because of the lack of a pronounced horizontal hydraulic gradient. The horizontal gradient has been reported to be very slight (0.0001 to 0.0002) (DOE-RL 1992). The direction of groundwater flow within the map area is inferred from water level data collected from wells in the B-pond area and the map area and by contaminant plumes (DOE-RL 1992). A potentiometric surface map for the upper part of the uppermost aquifer system for B-pond and surrounding area is presented in Figure 21. This map shows a flow direction to the west-southwest through the map area. The tritium plume map given in WHC (1992) shows the plume elongating to the southeast outside the map area. It can be inferred from these data that groundwater flows to the southwest in the eastern and central portion of the map area and to the south or southeast in the western portion of the map area.

2.3 VERTICAL GRADIENTS

Downward vertical gradients in the uppermost aquifer are caused by the B-Pond groundwater mound. Outside of the mound area and within the 200 East Area it is difficult to discern any vertical gradient because of small head differences. Near B-Pond wells 6-43-42J and 6-42-42B monitor the upper and lower parts of the uppermost aquifer, respectively, under unconfined conditions and have an approximate head difference of 0.6 m over a vertical length of about 9 m in a downward direction. The vertical downward hydraulic gradient in this area is about 0.06. Other nested wells, 299-E25-29P and 29Q, and 299-E25-30P and 30Q, 299-E25-32P and 32Q, and 299-E25-34 and 299-E25-28 are located near the Grout Treatment Facility and 216-A-29 Ditch. From the limited data available, the vertical head differences are interpreted to be so slight that they are indistinguishable from measurement error (DOE-RL 1992).

2.4 HYDRAULIC PROPERTIES

Hydraulic properties of transmissivity and/or hydraulic conductivity within the map area were previously determined from the results of aquifer tests, either constant discharge/recovery tests or instantaneous injection/

Figure 21. Potentiometric Surface Map for the Upper Part of the Uppermost Aquifer System in the Area of the 216-B-3 Pond System and Grout Treatment Facility (DOE-RL 1992).

withdrawal tests (WHC 1992). The constant discharge/recovery tests were analyzed using the Cooper-Jacob straight line method (Cooper and Jacob 1946). The injection/withdrawal tests were analyzed using either the Cooper method (Cooper et al. 1967) or the Bouwer-Rice method (Bouwer and Rice 1976; Bouwer 1989).

Table 1 lists transmissivity (T) and hydraulic conductivity (K) values from pumping tests of the upper uppermost aquifer system for five wells near or in the map area. Compilation of test data for the 200 East Aggregate Area can be found in Newcomer et al. (1992). Since T was the determined property, the equivalent K is given for comparison with laboratory results. The equivalent K was determined by dividing T by the thickness of the tested interval.

Table 1. Transmissivity and Hydraulic Conductivity Values for the Upper Uppermost Aquifer.

Well number	T ft ² /day	Tested interval thickness (ft)	Approximate equivalent K ft/day ^a	Geologic unit
2-E25-22	100,000 - 200,000	24	6,200 (2)	Ringold unit A
2-E25-32	>100,000	20	>5,000 (1.7)	Ringold unit A
2-E25-33	>100,000	20	>5,000 (1.7)	Ringold unit A
2-E25-34	>250,000	13	>19,000 (>7)	Ringold unit A
2-E25-35	>80,000	12	>6,500 (>2)	Ringold unit A
6-43-43	37,000	18	2,050 (0.7)	Hanford ^b lower gravel
6-44-42	76,000	19	4,000 (1.4)	Hanford ^b lower gravel

^aNumbers in parentheses are in cm/s.

^bHanford lower gravel sequence.

K = Hydraulic Conductivity.

T = Transmissivity.

The majority of the constant discharge/recovery pumping tests were single well tests with partially penetrating well screen. This testing approach does not allow calculation of the storage coefficient. Therefore, there is little information on storage properties for the uppermost aquifer.

The major shortcomings in analyzing injection/withdrawal tests are (1) the limited areal influence of the test, (2) potential sandpack influences, (3) limited stress applied to the aquifer, (4) difficulty in obtaining a complete data set in quick-response formations, and (5) the relatively low values of transmissivity for which the tests are interpretable.

Comparing equivalent hydraulic conductivities that are determined by pumping tests (Table 1) with saturated hydraulic conductivity determined from laboratory tests and reported in Smoot et al. (1989) shows that values from pumping tests are greater by orders of magnitude. This difference may be related to sampling and testing. Laboratory tests are for vertical K and involve small volumes of sediment that are repacked in the laboratory. These small volumes of sediment represent only tiny portions of the drilled intervals. Furthermore, heterogeneities over the recorded intervals cause preferential producing zones which are not detected by laboratory tests. Pumping tests, on the other hand, are for horizontal K and involve large volumes of *in situ* sediments in the vicinity of the wells tested. Another significant factor is the difficulty in analyzing coarse-grained sediments in the laboratory. (Gravel sequences in the Hanford and Ringold formations often contain gravel up to cobbles and boulders in size.) Laboratory tests only involve the finer portion of the samples because the coarse-grained fraction of samples is not collected by the sampling method or is removed prior to testing.

The ratio of horizontal to vertical conductivity at well 6-47-35 (2.3 km east-northeast of the northeast corner of the map area) ranges between 13 and 16 for sediments similar to those in the map area (Graham 1981). However, because of the recognized differences in sampling and testing, it would be inappropriate to try to calculate the ratio for the map area by using values in Table 1 and Smoot et al. (1989).

3.0 REFERENCES

- Alwin, J. A., 1970, *Clastic Dikes of the Touchet Beds, Southeastern Washington*, M.S. Thesis, Washington State University, Pullman, Washington.
- Baker, V. R., 1973, "Paleohydrology and Sedimentology of Lake Missoula Flooding in Eastern Washington," *Geological Society of America Special Paper* 144.
- Black, R. F., 1979, *Clastic Dikes of the Pasco Basin, Southeastern Washington*, RHO-BWI-C-64, Rockwell Hanford Operations, Richland, Washington.
- Bouwer, H., 1989, "The Bouwer and Rice Slug Test - An Update," *Ground Water*, vol. 27 no. 3, pp. 304-309.
- Bouwer, H. and R. C Rice, 1976, "A Slug Test for Determining Hydraulic Conductivity of Unconfined Aquifer with Completely or Partially Penetrating Wells," *Water Resources Research*, vol. 12 no. 3, pp. 423-428.
- Cooper, H. H., Jr., J. D. Bredehoeft, and I. S. Papadopoulos, 1967, "Response of a Finite-Diameter Well to an Instantaneous Charge of Water," *Water Resources Research*, vol. 3 no. 1, pp. 263-269.

- Cooper, H. H., Jr. and C. E. Jacob, 1946, "A Generalized Graphical Method for Evaluating Formation Constants and Summarizing Well Field History," *Transactions American Geophysical Union: 27(IV)*, pp. 526-534.
- Davis, J. D and C. D. Delaney, 1992, *The Site Characterization Work Plan - 200 Area Treated Effluent Disposal Facility W-049H*, WHC-SD-W049H-WP0001, Rev. 0, Westinghouse Hanford Company, Richland, Washington.
- Delaney, C. D., K. A. Lindsey, and S. P. Reidel, 1991, *Geology and Hydrology of the Hanford Site: A Standardized Text for Use in Westinghouse Hanford Company Documents and Reports*, WHC-SD-ER-TI-003, Westinghouse Hanford Company, Richland, Washington.
- DOE, 1988, *Consultation Draft Site Characterization Plan*, DOE/RW-0164, Vols. 1-9, Office of Civilian Radioactive Waste Management, U.S. Department of Energy, Washington, D.C.
- DOE-RL, 1992, *Annual Report of RCRA Groundwater Monitoring Projects at Hanford Site Facilities for 1991*, DOE/RL-92-03, U.S. Department of Energy, Richland Field Office, Richland, Washington.
- Fecht, K. R., 1978, *Geology of the Gable Mountain - Gable Butte Area: RHO-BWI-LD-5*, Rockwell Hanford Operations, Richland, Washington.
- Flint, R. F., 1938, "Summary of the Late Cenozoic Geology of Southeastern Washington," *American Journal of Science*, vol. 35, pp. 223-230.
- Graham, M. J., 1981, *Hydrology of the Separations Area*, RHO-ST-42, Rockwell Hanford Operations, Richland, Washington.
- Graham, M. J., G. V. Last, and K. R. Fecht, 1984, *An Assessment of Aquifer Intercommunication in the B Pond-Gable Mountain Pond Area of the Hanford Site*, RHO-RE-ST-12 P, Rockwell International, Rockwell Hanford Operations, Richland, Washington.
- Grolier, M. J. and J. W. Bingham, 1978, *Geology of Parts of Grant, Adams, and Franklin Counties, East-Central Washington*, Bulletin 71, Division of Geology and Earth Resources, Department of Natural Resources, State of Washington.
- Jenkins, O. P., 1925, "Clastic Dikes of Eastern Washington and Their Geologic Significance," *American Journal of Science*, vol. X, no. 57, pp. 234-246.
- Kasza, G. L., M. J. Hartman, F. N. Hodges, and D. C. Weekes, 1992, *Ground Water Maps of the Hanford Site, December 1991*, WHC-EP-0394-4, Westinghouse Hanford Company, Richland, Washington.
- Last, G. V., B. N. Bjornstad, M. P. Bergeron, D. W. Wallace, D. R. Newcomer, J. A. Schramke, M. A. Chamness, C. S. Cline, S. P. Airhart, and J. S. Wilbur, 1989, *Hydrogeology of the 200 Areas Low-Level Burial Grounds - An Interim Report*, PNL-6820, Pacific Northwest Laboratory, Richland, Washington.

- Lindsey, K. A., B. N. Bjornstad, and M. P. Connelly, 1991, *Geologic Setting of the 200 West Area: An Update*, WHC-SD-EN-TI-008, Westinghouse Hanford Company, Richland, Washington.
- Lindsey, K. A., B. N. Bjornstad, J. W. Lindberg, and K. M. Hoffmann, 1992, *Geologic Setting of the 200 East Area: An Update*, WHC-SD-EN-TI-012, Westinghouse Hanford Company, Richland, Washington.
- Lupher, R. L., 1944, "Clastic Dikes of the Columbia Basin Region, Washington and Idaho," *Geologic Society of America Bulletin*, vol. 55, pp. 1431-1462.
- Myers, C. W., S. M. Price, J. A. Caggiano, M. P. Cochran, W. J. Czimer, N. J. Davidson, R. C. Edwards, K. R. Fecht, G. E. Holmes, M. G. Jones, J. R. Kunk, R. D. Landon, R. K. Ledgerwood, J. T. Lillie, P. E. Long, T. H. Mitchell, E. H. Price, S. P. Reidel, and A. M. Tallman, 1979, *Geologic Studies of the Columbia Plateau: A Status Report*, RHO-BWI-ST-4, Rockwell Hanford Operations, Richland, Washington.
- Newcomb, R. C., 1962, *Hydraulic Injection of Clastic Dikes in the Touchet Beds, Washington, Oregon, and Idaho*, Geological Society of the Oregon Country [Abstract], v. 28, no. 10.
- Newcomer, D. R., 1990, *Evaluation of Hanford Site Water-Table Changes - 1980 to 1990*, PNL-7498, Pacific Northwest Laboratory, Richland, Washington.
- Newcomer, D. R., M. A. Chamness, D. L. McAlister, R. J. Brockman, A. W. Pearson, S. T. Teel, 1992, *Unconfined Aquifer Hydrologic Test Data Package for the 200 East Area*, WHC-SD-EN-TI-030, Westinghouse Hanford Company, Richland, Washington.
- Reidel, S. P. and K. R. Fecht, 1981, "Wanapum and Saddle Mountains Basalt in the Cold Creek Syncline Area," in *Subsurface Geology of the Cold Creek Syncline*, RHO-BWI-ST-14, Rockwell Hanford Operations, Richland, Washington.
- Smoot, J. L., J. E. Szecsody, B. Sagar, G. W. Gee, and C. T. Kincaid, 1989, *Simulations of Infiltration of Meteoric Water and Contaminant Plume Movement in the Vadose Zone at Single Shell Tank 241-T-106 at the Hanford Site*, WHC-EP-0332, Westinghouse Hanford Company, Richland, Washington.
- WHC, 1992, *Hydrogeologic Model for the 200 East Aggregate Area*, WHC-SD-TI-019, Rev. 0, Westinghouse Hanford Company, Richland, Washington.

Appendix D

Ecology^(a)

-
- (a) This appendix was extracted from Section 4.3 of PNL-6415, Rev. 4. (C. E. Cushing, Editor. December 1991. *Hanford Site National, Environmental Policy Act (NEPA) Characterization*. PNL-6415, Rev. 4, Pacific Northwest Laboratory, Richland, Washington.)

Appendix D

Ecology

The Hanford Site is a relatively large, undisturbed area (1450 km² [~560 mi²]) of shrub-steppe that contains numerous plant and animal species adapted to the region's semiarid environment. The site consists of mostly undeveloped land with widely spaced clusters of industrial buildings located along the western shoreline of the Columbia River and at several locations within the site's interior. The industrial buildings are interconnected by roads, railroads, and electrical transmission lines. The major facilities and activities occupy about 6% of the total available land area, and their impact on the surrounding ecosystems is minimal. Most of the Hanford Site has not experienced tillage or livestock grazing since the early 1940s. The Columbia River flows through the Hanford Site, and although the river flow is not directly impeded by artificial dams within the Hanford Site, the historical daily and seasonal water fluctuations have been changed by dams upstream and downstream of the site (Rickard and Watson 1985). The Columbia River and other water bodies on the Hanford Site provide habitat for aquatic organisms. These habitats are discussed in detail in Cushing (1991). The Columbia River is also accessible for public recreational use and commercial navigation. Other descriptions of the ecology of the Hanford Site can be found in ERDA (1975), Rogers and Rickard (1977), Jamison (1982), and Watson et al. (1984), among others.

D.1 Terrestrial Ecology

D.1.1 Vegetation

The Hanford Site, located in southeastern Washington, has been botanically characterized as a shrub-steppe region (Daubenmire 1970). Because of the aridity, the productivity of both plants and animals is relatively low compared with other natural communities. In the early 1800s, the dominant plant in the area was big sagebrush with an understory of perennial bunchgrasses, especially Sandberg's bluegrass and bluebunch wheatgrass. With the advent of settlement that brought livestock grazing and crop raising, the natural vegetation mosaic was opened to a persistent invasion by alien annuals, especially cheatgrass. Today cheatgrass is the dominant plant on fields that were cultivated 40 years ago. Cheatgrass is also well established on rangelands at elevations less than 244 m (800 ft) (Rickard and Rogers 1983). Wildfires in the area are common; the most recent extensive fire in 1984 significantly altered the shrub component of the vegetation. The dryland areas of the Hanford Site were treeless in the years before land settlement; however, for several decades before 1943, trees were planted and irrigated on most of the farms to provide windbreaks and shade. When the farms were abandoned in 1943, some of the trees died but others have persisted, presumably because their roots are deep enough to contact

groundwater. Today these trees serve as nesting platforms for several species of birds, including hawks, owls, ravens, magpies, and great blue herons, and as night roosts for wintering bald eagles (Rickard and Watson 1985).

The release of water used as industrial process coolant streams at the Hanford Site facilities created several semipermanent artificial ponds that did not exist previously. Over the years, stands of cattails, reeds, and trees, especially willow, cottonwood, and Russian olive, have developed around the ponds. These ponds are ephemeral and will disappear if the industrial release of water is terminated; in fact, many of these have already disappeared.

More than 500 species of plants have been identified on the Hanford Site (Sackschewsky et al. 1992), and more than 100 species of plants have been identified in the 200 Area Plateau (ERDA 1975). The dominant plants on the 200 Area Plateau are big sagebrush, rabbitbrush, cheatgrass, and Sandberg's bluegrass, with cheatgrass providing half of the total plant cover. Cottonwood, willows, cattails, and bullrushes grow along the banks of ponds and ditches. Cheatgrass and Russian thistle, which are annuals introduced to the United States from Eurasia in the late 1800s, invade areas where the ground surface has been disturbed. The main links in the food web leading to humans are through mule deer and chukar partridge. Other significant pathways leading to humans through terrestrial food webs would be through geese, ducks, upland game birds, elk, and asparagus.

D.1.2 Insects

More than 300 species of terrestrial and aquatic insects have been found on the Hanford Site (ERDA 1975). Grasshoppers and darkling beetles are among the more conspicuous groups and, along with other species, are important in the food web of the local birds and mammals. Links in the food web leading from grasshoppers to the Swainson's hawk are of concern because the Swainson's hawk is a federal candidate for threatened and endangered designation.

D.1.3 Reptiles and Amphibians

Twelve species of amphibians and reptiles are known to occur on the Hanford Site (Fitzner and Gray 1991). The occurrence of these species is infrequent when compared with similar fauna of the southwestern United States.

D.1.4 Birds

Fitzner and Gray (1991) and Landeen et al. (1992) have presented data on birds observed on the Hanford Site. The horned lark and western meadowlark are the most abundant nesting birds in the shrub-steppe. Thirty-six species of the more common birds present on the Hanford Site are listed in Cushing (1991).

D.1.4.1 Birds Inhabiting Riverine Habitats

The most abundant game birds nesting in riverine habitats are the Canadian goose (Hanson and Eberhardt 1971), ring-necked pheasant, and California quail. Mallards also nest there but in smaller numbers. The Hanford Site is located in the Pacific Flyway; in addition, a major sandhill crane flyway passes over the site. Islands in the river also provide nesting sites for thousands of ring-billed gulls and California gulls and a few hundred Forster's terns. Shoreline trees serve as nesting sites for four separate colonies of great blue herons.

Bald eagles regularly visit the riverine habitat in winter because of the relative freedom from human disturbances, the abundance of food, and the presence of trees for daytime perches and nighttime roosts. Large numbers of cliff and bank swallows nest on the steep bluffs overlooking the Columbia River. White pelicans, double-crested cormorants, common loons, and ospreys are present along the Columbia River during spring months, but they have not been observed to nest there. Many species of songbirds nest in the narrow corridor of streamside thickets along the Columbia River.

Wastewater ponds at the Hanford Site are important habitats for songbirds, shore birds, ducks, and geese (Fitzner and Price 1973; Fitzner and Rickard 1975; Fitzner and Schreckhise 1979). The American coot is an abundant aquatic nesting bird on these sites.

D.1.4.2 Birds Inhabiting Terrestrial Habitats

The game birds inhabiting terrestrial habitats at Hanford are the chukar, gray partridge, and mourning dove. Sage grouse populations have declined on the Hanford Site since the 1940s, and it is likely that there are no nesting grouse on the site at this time. In recent years, the number of nesting ferruginous hawks has increased, at least in part because the hawks have accepted steel powerline towers as nesting sites. Only about 50 pairs are believed to be nesting in the state of Washington. Other raptors that nest on the Hanford Site are the prairie falcon, northern harrier, red-tailed hawk, Swainson's hawk, and kestrel. Burrowing owls, great horned owls, barn owls, and long-eared owls also nest on the site but in smaller numbers.

D.1.5 Mammals

Approximately 39 species of mammals have been identified on the Hanford Site (Fitzner and Gray 1991). They are listed in Cushing (1991).

D.1.5.1 Mammals Inhabiting Riverine Habitats

The Columbia River and adjacent shoreline support populations of beaver, muskrat, mink, raccoon, and striped skunk. Mule deer forage on shoreline plants and seek shade provided by shoreline trees, especially during the hot, dry summer months.

D.1.5.2 Mammals Inhabiting Terrestrial Habitats

The largest vertebrate predator inhabiting the Hanford Site is the coyote, which ranges all across the site. Coyotes have been a major cause of destruction of Canada goose nests on Columbia River Islands, especially islands upstream from the abandoned Hanford townsite. Bobcats and badgers also inhabit the Hanford Site but in low numbers.

Black-tailed jackrabbits are common on the Hanford Site, mostly associated with mature stands of sagebrush. Cottontails are also common but appear to be more closely associated with the areas surrounding onsite laboratory and industrial facilities. Townsend ground squirrels occur in colonies of various sizes scattered across the Hanford Site but marmots are scarce. The most abundant mammal inhabiting the site is the Great Basin pocket mouse. Other small mammals include the deer mouse, harvest mouse, grasshopper mouse, montane vole, vagrant shrew, and Merriam's shrew. Seven species of bats inhabit the Hanford Site, occurring mostly as fall or winter migrants.

A herd of Rocky Mountain elk is present on the Arid Lands Ecology (ALE) Reserve. It is believed that these animals immigrated to the ALE Reserve from the Cascade Mountains in the early 1970s. This herd had grown from approximately 6 animals in 1972 to 119 in spring of 1992. Elk remain on the ALE Reserve because of the protection the area provides from human disturbance. Mule deer are found throughout the Hanford Site, although areas of highest concentrations are on the ALE Reserve and along the Columbia River. Deer populations on the Hanford Site appear to be relatively stable.

D.2 Aquatic Ecology

There are two types of natural aquatic habitats on the Hanford Site. One is the Columbia River, which flows along the northern and eastern edges of the Hanford Site, and the other is provided by the small spring-streams and seeps located mainly on the ALE site in the Rattlesnake Hills. Several artificial water bodies, both ponds and ditches, have been formed as a result of wastewater disposal practices associated with the operation of the reactors and separation facilities. These are temporary and will vanish when activities cease, but while present, they form established aquatic ecosystems (except West Pond) complete with representative flora and fauna (Emery and McShane 1980). West Pond is created by a rise in the water table in the 200 Areas and is not fed by surface flow. Thus, it is alkaline and has a greatly restricted complement of biota.

D.2.1 The Columbia River

The Columbia River is the dominant aquatic ecosystem on the Hanford Site and supports a large and diverse community of plankton, benthic invertebrates, fish, and other communities. It is the fifth largest river in North America and has a total length of about 2000 km (~1240 mi) from its origin in British Columbia to its mouth at the Pacific Ocean. The Columbia has been dammed both upstream and downstream from the Hanford Site, and the reach flowing through the area is the last free-flowing, but

regulated, reach of the Columbia River in the United States. Plankton populations in the Hanford Reach are influenced by communities that develop in the reservoirs of upstream dams, particularly Priest Rapids Reservoir, and by manipulation of water levels below by dam operations in downstream reservoirs. Phytoplankton and zooplankton populations at Hanford are largely transient, flowing from one reservoir to another. There is generally insufficient time for characteristic endemic groups of phytoplankton and zooplankton to develop in the Hanford Reach. No tributaries enter the Columbia during its passage through the Hanford Site.

The Columbia River is a very complex ecosystem because of its size, the number of alterations, the diversity of the biota, and the size and diversity of its drainage basin. Streams in general, especially smaller ones, usually depend on organic matter from outside sources (terrestrial plant debris) to provide energy for the ecosystem. Large rivers, particularly the Columbia River with its series of large reservoirs, contain significant populations of primary energy producers (algae, plants) that contribute to the basic energy requirements of the biota. Phytoplankton (free-floating algae) and periphyton (sessile algae) are abundant in the Columbia River and provide food for herbivores such as immature insects, which in turn are consumed by carnivorous species. A complete discussion of phytoplankton, periphyton, macrophytes, zooplankton, and benthic organisms appears in Cushing (1991).

D.2.1.1 Fish

Gray and Dauble (1977) list 43 species of fish in the Hanford Reach of the Columbia River. The brown bullhead (*Ictalurus nebulosus*) has been collected since 1977, bringing the total number of fish species identified in the Hanford Reach to 44. Of these species, the chinook salmon, sockeye salmon, coho salmon, and steelhead trout use the river as a migration route to and from upstream spawning areas and are of the greatest economic importance. Both the fall chinook salmon and steelhead trout also spawn in the Hanford Reach. The relative contribution of upper river bright stocks to fall chinook salmon runs in the Columbia River increased from about 24% of the total in the early 1980s to 50% to 60% of the total by 1988 (Dauble and Watson 1990). The destruction of other mainstream Columbia spawning grounds by dams has increased the relative importance of the Hanford Reach spawning (Watson 1970, 1973).

The shad, another anadromous species, may also spawn in the Hanford Reach. The upstream range of the shad has been increasing since 1956. The shad is not dependent on specific current and bottom conditions required by the salmonids for spawning and has apparently found favorable conditions for reproduction throughout much of the Columbia River and the Snake River. Other fish of importance to sport fishermen are the whitefish, sturgeon, smallmouth bass, crappie, catfish, walleye, and perch. Large populations of rough fish including carp, shiners, suckers, and squawfish are also present.

D.2.2 Spring Streams

The small spring streams, such as Rattlesnake and Snively springs, contain diverse biotic communities and are extremely productive (Cushing and Wolf 1984). The aquatic insect production is fairly high as compared to mountain streams (Gaines 1987). The macrobenthic biota varies from site to site and is related to the proximity of colonizing insects and other factors. Rattlesnake Springs, on the western side of the Hanford Reservation, forms a small surface stream that flows for about 2.5 km (1.6 mi) before disappearing into the ground as a result of seepage and evapotranspiration. Base flow of this stream is about 0.01 m³/sec (0.4 cfs) (Cushing and Wolf 1982). The stream is of ecological importance because it provides a source of water to terrestrial animals in an otherwise arid part of the reservation. Snively Springs, located farther west and at a higher elevation than Rattlesnake Springs, apparently does not contribute to the flow of Rattlesnake Springs (Brown 1970), but probably flows to the west and off the Hanford Site. An inventory of the many springs occurring on the Rattlesnake Hills has been published by Schwab et al. (1979). Limited physical and chemical data are included for each site.

D.2.3 Wetlands

Several habitats on the Hanford Site could be considered as wetlands. The primary wetland site is the riparian zone bordering the Columbia River. The zone is extensively impacted by both seasonal water level fluctuations and daily variations related to power generation at Priest Rapids Dam immediately upstream from the site. Other extensive areas of wetlands can be found within the Saddle Mountain National Wildlife Refuge and the Wahluke Wildlife Refuge Area; these two areas encompass all the lands extending from the north bank of the Columbia River northward to the site boundary and east of the Columbia River down to Ringold Springs. Some wetlands habitat of less than a hectare in size exists in the riparian zones of some of the larger spring streams on the ALE Reserve of the Hanford Site.

D.2.4 Temporary Water Bodies

The temporary wastewater ponds and ditches have been in place for as long as two decades, although many have been eliminated. Rickard et al. (1981) discussed the ecology of Gable Mountain Pond, one of the former major lentic sites. Emery and McShane (1980) presented the ecological characteristics of all the temporary sites.

D.3 Threatened and Endangered Species

Threatened and endangered plants and animals identified on the Hanford Site, as listed by the federal government (50 CFR 17) and Washington State (Washington State Natural Heritage Program 1990), are shown in Cushing (1991). No plants or mammals on the federal list of Endangered and

Threatened Wildlife and Plants (DOI 1986; 50 CFR 17.11, 17.12) are known to occur on the Hanford Site. There are, however, several species of both plants and animals that are under consideration for formal listing by the federal government and Washington State.

D.3.1 Plants

Four species of plants are included in the Washington State listing. Columbia milk-vetch (*Astragalus columbianus* Barneby) and Hoover's desert parsley (*Lomatium tuberosum*) are listed as threatened, and yellowcress (*Rorippa columbiae* Suksd.) and northern wormwood (*Artemisia campestris* ssp. *borealis* var. *wormskioldii*) are designated as endangered. Columbia milk-vetch occurs on dry land benches along the Columbia River in the vicinity of Priest Rapids Dam, Midway, and Vernita; it also has been found on top of Umtanum Ridge and in Cold Creek Valley near the present vineyards. Hoover's desert parsley grows on steep talus slopes in the vicinity of Priest Rapids Dam, Midway, and Vernita. Yellowcress occurs in the wetted zone of the water's edge along the Columbia River. Northern wormwood is known to occur near Beverley and could inhabit the northern shoreline of the Columbia River across from the 100 Areas.

D.3.2 Animals

The federal government lists the Aleutian Canada goose (*Branta canadensis leucopareia*) and the bald eagle (*Haliaeetus leucocephalus*) as threatened and the peregrine falcon (*Falco peregrinus*) as endangered. The state of Washington lists, in addition to the peregrine falcon, Aleutian Canada goose, bald eagle, the white pelican (*Pelecanus erythrorhynchos*) and sandhill crane (*Grus canadensis*) as endangered and the ferruginous hawk (*Buteo regalis*) as threatened. The peregrine falcon is a casual migrant to the Hanford Site and does not nest here. The bald eagle is a regular winter resident and forages on dead salmon and waterfowl along the Columbia River; it does not nest on the Hanford Site. Increased use of power poles for nesting sites by the ferruginous hawk on the Hanford Site has been noted. Washington State Bald Eagle Protection Rules were issued in 1986 (WAC-232-12-292). These rules require DOE to prepare a management plan to mitigate eagle disturbance; such a plan is currently in preparation. The Endangered Species Act of 1973 will also require that section 7 consultation be undertaken when any action is taken that may jeopardize the existence of, destroy, or adversely modify habitat of the bald eagle or other endangered species.

D.4 References

50 CFR 17. 1986. U.S. Department of the Interior (DOI). "Endangered and Threatened Wildlife and Plants." *U.S. Code of Federal Regulations*.

Brown, R.E. 1970. *Interrelationships of Geologic Formations and Processes Affecting Ecology as Exposed at Rattlesnake Springs, Hanford Project*. BNWL-B-29, Pacific Northwest Laboratory, Richland, Washington.

Cushing, C.E., Editor. 1991. *Hanford Site National Environmental Policy Act (NEPA) Characterization*. PNL-6415, Rev. 4, Pacific Northwest Laboratory, Richland, Washington.

Cushing, C.E., and E.G. Wolf. 1984. "Primary Production in Rattlesnake Springs, a Cold Desert Spring-Stream." *Hydrobiologia* 114:229-236.

Cushing, C.E., and E.G. Wolf. 1982. "Organic Energy Budget of Rattlesnake Springs, Washington." *Am. Midl. Nat.* 107(2):404-407.

Daubenmire, R. 1970. *Steppe Vegetation of Washington*. Technical Bulletin 62, Experimental Station, Washington State University, Pullman, Washington.

Dauble, D.D., and D.G. Watson. 1990. *Spawning and Abundance of Fall Chinook Salmon (Oncorhynchus tshawytscha) in the Hanford Reach of the Columbia River, 1948-1988*. PNL-7289, Pacific Northwest Laboratory, Richland, Washington.

Emery, R.M., and M.C. McShane. 1980. "Nuclear Waste Ponds and Streams on the Hanford Site: An Ecological Search for Radiation Effects." *Health Phys.* 38:787-809.

Fitzner, R.E., and R.H. Gray. 1991. "The Status, Distribution, and Ecology of Wildlife on the U.S. DOE Hanford Site: A Historical Overview of Research Activities." *Environ. Monit. Assess.* 18:173-202.

Fitzner, R.E., and R.G. Schreckhise. 1979. *Nesting Biology. Part 1 of the American Coot (Fulica americana) on the Hanford Site*. PNL-2462, Pacific Northwest Laboratory, Richland, Washington.

Fitzner, R.E., and W.H. Rickard. 1975. *Avifauna of Waste Ponds, ERDA Hanford Reservation, Benton County, Washington*. BNWL-1885, Pacific Northwest Laboratory, Richland, Washington.

Fitzner, R.E., and K.R. Price. 1973. *The Use of Hanford Waste Ponds by Waterfowl and Other Birds*. BNWL-1738, Pacific Northwest Laboratory, Richland, Washington.

Gaines, W.E. 1987. *Secondary Production of Benthic Insects in Three Cold Desert Streams*. PNL-6286, Pacific Northwest Laboratory, Richland, Washington.

Gray, R.H., and D.D. Dauble. 1977. "Checklist and Relative Abundance of Fish Species from the Hanford Reach of the Columbia River." *Northwest Sci.* 51:208-215.

- Hanson, W.C., and L.L. Eberhardt. 1971. *A Columbia River Goose Population 1950-1970*. Wildlife Monograph No. 28, Wildlife Society, Bethesda, Maryland.
- Jamison, J.D. 1982. *Standardized Input for Hanford Environmental Impact Statements Part II: Site Descriptions*, pp.9.1-9.16. PNL-3509, Pt. 2, Pacific Northwest Laboratory, Richland, Washington.
- Landeem, D.S., A.R. Johnson, and R.M. Mitchell. 1992. *Status of Birds at the Hanford Site in Southeastern Washington*. WHC-EP-0402, Rev. 1, Westinghouse Hanford Company, Richland, Washington.
- Rickard, W.H., and D.G. Watson. 1985. "Four Decades of Environmental Change and Their Influences Upon Native Wildlife and Fish on the Mid-Columbia River, Washington, U.S.A." *Environ. Conserv.* 12:241-248.
- Rickard, W.H., and L.E. Rogers. 1983. "Industrial Land Use and the Conservation of Native Biota in the Shrub-Steppe Region of Western North America." *Environ. Conserv.* 10:205-211.
- Rickard, W.H., R.E. Fitzner, and C.E. Cushing. 1981. "Biological Colonization of an Industrial Pond." *Environ. Conserv.* 8:241-247.
- Rogers, L.E., and W.H. Rickard. 1977. *Ecology of the 200 Area Plateau Waste Management Environs: A Status Report*. PNL-2253, Pacific Northwest Laboratory, Richland, Washington.
- Sackschewsky, M.R., D.S. Landeen, G.I. Baird, W.H. Rickard, and J.L. Downs. 1992. *Vascular Plants of the Hanford Site*. WHC-EP-0554, Westinghouse Hanford Company, Richland, Washington.
- Schwab, G.E., R.M. Colpitts, Jr., and D.A. Schwab. 1979. *Spring Inventory of the Rattlesnake Hills*. W.K. Summers and Associates, Inc., Socorro, New Mexico.
- U.S. Energy Research and Development Administration (ERDA). 1975. *Final Environmental Impact Statement of Waste Management Operations, Hanford Reservation, Richland, Washington*, 2 vols. ERDA-1538, U.S. Energy Research and Development Administration, Washington, D.C.
- Watson, E.C., C.D. Becker, R.E. Fitzner, K.A. Gano, C.L. Imhoff, R.F. McCallum, D.A. Myers, T.L. Page, K.R. Price, J.V. Ramsdell, D.G. Rice, D.L. Schreiber, L.A. Skumatz, D.J. Sommer, J.J. Tawil, R.W. Wallace, and D.G. Watson. 1984. *Environmental Characterization of Two Potential Locations at Hanford for a New Production Reactor*. PNL-5275, Pacific Northwest Laboratory, Richland, Washington.
- Watson, D.G. 1973. *Fall Chinook Salmon Population Census*. BNWL-1750, Pacific Northwest Laboratory, Richland, Washington.

Watson, D.G. 1970. *Fall Chinook Salmon Spawning in the Columbia River Near Hanford 1947-1969*. BNWL-1515, Pacific Northwest Laboratory, Richland, Washington.

Appendix E

Waste Inventory^(a)

-
- (a) This document is a reproduction of document number WHC-SD-WM-TI-528, Rev. 0, prepared by Westinghouse Hanford Company. (D. W. Hendrickson and J. M. Conner. 1993. *Grout Treatment Facility Waste Feed Projections*. WHC-SD-WM-TI-528, Rev. 0. Westinghouse Hanford Company, Richland, Washington.)

The version of the waste feed projection document presented in this appendix was revised after the performance assessment was completed to incorporate minor corrections to the inventory projections. The revised version, WHC-SD-WM-TI-528 Rev. 1, is included in Appendix R. In the version presented here, the tables on which Table 1-4 are printed were replaced with the Rev. 1 pages in order to show the exponents in the far right column (the exponents were missing on the Rev. 0 pages).

SUPPORTING DOCUMENT

1. Total Pages 126

2. Title

Grout Treatment Facility Waste Feed Projections

3. Number

WHC-SD-WM-TI-528

4. Rev No.

0

5. Key Words

DST, Double-Shell Tank, Waste, Grout, Pretreatment

6. Author

Name: D. W. Hendrickson

J. M. Conner

Signatures

Organization/Charge Code 7E220/D44H1

APPROVED FOR *KMB*
PUBLIC RELEASE *2/17/93*

7. Abstract

This document presents, evaluates, and summarizes analytical, technical, and previous operational history data with regard to the characterization of Hanford Double-Shell Tank wastes currently proposed for disposal through the Hanford Grout Disposal Program.

8. PURPOSE AND USE OF DOCUMENT - This document was prepared for use within the U.S. Department of Energy and its contractors. It is to be used only to perform, direct, or integrate work under U.S. Department of Energy contracts. This document is not approved for public release until reviewed.

PATENT STATUS - This document copy, since it is transmitted in advance of patent clearance, is made available in confidence solely for use in performance of work under contracts with the U.S. Department of Energy. This document is not to be published nor its contents otherwise disseminated or used for purposes other than specified above before patent approval for such release or use has been secured, upon request, from the Patent Counsel, U.S. Department of Energy Field Office, Richland, WA.

Records removed per WHC Legal KMB 2/17/93
DISCLAIMER - This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

10. RELEASE STAMP

OFFICIAL RELEASE 63
BY WHC
DATE FEB 17 1993

Sta #4

9. Impact Level 3E

WHC-SD-WM-TI-528, Rev. 0

**GROUT TREATMENT FACILITY
WASTE FEED PROJECTIONS**

Prepared for
WESTINGHOUSE HANFORD COMPANY

by

D. W. Hendrickson
Westinghouse Hanford Company

J. M. Conner
Westinghouse Hanford Company

January 1993

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 0

Grout Treatment Facility Waste Feed Projections

TABLE OF CONTENTS

	<u>Page</u>
1.0 INTRODUCTION	1-1
2.0 WASTE DATA EVALUATION METHODS AND HISTORY	2-1
2.1 Wastes Described by Direct Sampling and Analysis	2-1
2.2 Wastes Described by Process and Transfer History	2-2
2.3 Wastes Described by Pretreatment Flowsheets	2-4
3.0 DATA HANDLING TECHNIQUES	3-1
3.1 Data Handling for Existent Waste Samples	3-3
3.1.1 Existent Dilute Waste Sample Data	3-4
3.1.2 Existent Concentrated Waste Sample Data	3-4
3.2 Data Handling for Process History Samples	3-5
3.2.1 Referenced Historical Process Analyses	3-5
3.2.2 Future Evaporator Product Estimation	3-5
3.2.3 Process Analyses for Previous Evaporator Products	3-6
3.3 Data Handling for Pretreatment Low-Level Streams	3-8
3.4 Data Summarization and Interpretation	3-9
3.4.1 Application of Uniform Decay Date	3-9
3.4.2 Evaluation of Dilute Waste Requirements	3-10
3.4.3 Use and Application of Limiting Values	3-11
3.4.4 Analytical Errors	3-12
3.4.5 Data Summary	3-13
3.5 Recommendations on Data Usage	3-14
4.0 SPECIAL ESTIMATES OF CRITICAL ISOTOPES	4-1
4.1 ¹³⁵ Cesium Estimation	4-1
4.1.1 Back-Decay of ¹³⁷ Cesium Data	4-3
4.1.2 ¹³⁵ Cesium Production	4-3
4.1.3 ¹³⁵ Cesium Estimate Usage	4-4
4.2 ²³⁷ Neptunium Estimation	4-4
4.2.1 Revision of ²⁴¹ Americium Estimates	4-5
4.2.2 Revision of ²³⁷ Neptunium Estimates	4-8
4.3 ²²⁶ Radium Estimation	4-9
4.4 ¹²⁹ Iodine Estimation	4-11
4.5 ¹²⁶ Tin Estimation	4-12
4.6 ⁹⁹ Technetium Estimation	4-12
4.7 ⁹⁴ Niobium Estimation	4-13
4.8 ⁷⁹ Selenium Estimation	4-13
4.9 ¹⁴ Carbon Estimation	4-13
4.10 ²³⁸ Uranium Estimation	4-14
4.11 Special Estimate Summary	4-15
5.0 REFERENCES	5-1
APPENDIX	A-i

WHC-SD-WM-TI-528, Rev. 0

LIST OF TABLES

<u>TABLE</u>	<u>Page</u>
1: Grout Treatment Facility Waste Volume Expectations	2-2
2: Tank 241-AN-104 Waste Source History	3-6
3: Tank 241-AN-105 Waste Source History	3-7
4: Grout Treatment Facility Waste Projection	3-17
5: ORIGEN2 Yield Per Metric Ton of Fuel	4-2
6: Waste ¹³⁷ Cs Activity	4-4
7: ²⁴¹ Americium Sources	4-6
8: Special Estimates of Critical Isotopes	4-16

LIST OF FIGURES

	<u>Page</u>
Figure 1: Waste Source Volume Distribution for Grout Disposal	2-3
Figure 2: Grout Feed Material Data Flowsheet	3-2
Figure 3: Profile of DSSF Family Wastes Relative to Sodium	3-3
Figure 4: Distribution of Am-241 Sources to Grout (Assumes maximum allowable in 4AN/5AN)	4-7

WHC-SD-WM-TI-528, Rev. 0

GROUT TREATMENT FACILITY
WASTE FEED PROJECTIONS

1.0 INTRODUCTION

The *Final Environmental Impact Statement, Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington* [HDW-EIS] (DOE 1987) evaluated disposal alternatives for Double-Shell Tank (DST) wastes at the Hanford Site. The responsive Record of Decision [ROD] (DOE 1988) selected cementitious disposal via the Hanford Grout Disposal Program (HGDP) as the preferable alternative for the disposal of low-level radioactive liquid wastes contained in Hanford's DSTs.

Since the issuance of the HDW-EIS and ROD (DOE 1987, 1988) extensive review and analysis has been conducted to determine the specific nature and characteristics of DST wastes to be received and disposed under the HGDP.

The purpose of this document is to describe the current information available on the character of wastes identified as HGDP feed material. Grout feed material is to be composed of the low-level liquid pretreated residuals and supernatant fractions of all DSTs. Dilute waste materials contained within DSTs are, in large part, expected to be evaporated prior to HGDP processing in order to ease tank farm capacity constraints.

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 0

2.0 WASTE DATA EVALUATION METHODS AND HISTORY

The DST wastes described in this document have been evaluated in four general manners. The first such manner is that of direct sampling and analysis for the purpose of characterization. The second is the use of historical process data surrounding material transfers and historical and expected Evaporator/Crystallizer campaign conduct. Thirdly, pretreatment flowsheet information is used to describe approximately one half of expected waste receipts to the HGPD. Finally, data resulting from the above evaluations are compared to relevant reactor history codes and Hanford Site documents. This last comparative evaluation is contained in §4.0.

A summary of expected wastes described in this document is contained in Table 1 and depicted in Figure 1. These wastes comprise the supernatant liquid fraction of current, future and pretreated DST contents expected to be received by the Hanford Grout Disposal Program. These wastes and their volumes are described by Hanlon (1992), and Lowe (1991), and are further developed within this document.

2.1 Wastes Described by Direct Sampling and Analysis

The DST wastes described in this document for which information gathered was by direct sampling and analysis include concentrated waste tanks 241-AN-106, 241-AW-101, and 241-AN-103, and dilute waste tanks 241-AP-103, 241-AW-106, and 241-AW-102. Further discussion of the history of information accumulation on this waste category is provided below.

The first significant milestone in the evaluation of concentrated DST wastes was achieved in 1988 with the initial issuance of "Methods and Data for Use in Determining Source Terms for the Grout Disposal Program" (Hendrickson 1990). That document describes the analyses of the supernatant fractions of three DST waste tanks expected, at that time, to be representative of all wastes to be received at the HGDP. The three wastes discussed were those contained in tanks 241-AN-106, 241-AW-101, and 241-AN-103. These wastes are, respectively, concentrated phosphate wastes from N-Reactor, concentrated Facilities waste termed Double-Shell Slurry Feed (DSSF), and Double-Shell Slurry (DSS).

Additional milestones were achieved in the completion of detailed analyses of tanks 241-AN-106 and 241-AW-101 (Welsh 1991a and 1991b). These detailed analyses allowed significant analytical refinement and reduction in the estimation of waste variability (expressed as the standard deviation) for these wastes.

Characterization efforts in support of projected Evaporator/Crystallizer operation led to the sampling and analysis of dilute non-complexed wastes contained in tanks 241-AP-103, 241-AW-106, and 241-AW-102 between June and December 1991.

WHC-SD-WM-TI-528, Rev. 0

TABLE 1: Grout Treatment Facility Waste Volume Expectations			
General Type	Description	Tanks	Volume (L x 10 ⁶)
DSSF ¹ Family	Concentrated Phosphate	241-AN-106	3.67
	Existent DSSF	241-AW-101	3.83
		241-AP-105	3.15
		241-AN-104	3.02
		241-AN-105	4.27
	Future DSSF	Undefined	30.28
	DSS	241-AN-103	3.55
	Dilute Wastes	241-AP-106 and others	9.05
Pretreated Wastes (Low-Level Residual)	NCAW	241-AZ-101	3.60
		241-AZ-102	3.61
	NCRW	241-AW-103	12.87
		241-AW-105	
	PFP	241-SY-102 and PFP	2.08
	Complexed Concentrate	241-SY-101 241-SY-103 241-AN-102 241-AN-107	39.0
Total			122.0

2.2 Wastes Described by Process and Transfer History

Wastes described in this document for which information gathered was by process and transfer history include concentrated waste tanks 241-AP-105, 241-AN-104, and 241-AN-105, and dilute waste tank 241-AP-106. Future evaporator products are estimated based on current dilute waste compositions and expected evaporative processing. Further discussion of the history of information accumulation on this waste category is provided below.

Detailed historical analysis of waste material transfers and Evaporator/Crystallizer operation allowed the development of waste composition estimates for dilute waste tank 241-AP-106 and DSSF tank 241-AP-105 (Hendrickson and Welsh 1992a, and 1992b). These material estimates were developed to support sampling and analysis of these tanks.

¹

Waste descriptions and acronyms are detailed in the following text and in Hanlon (1992).

WHC-SD-WM-TI-528, Rev. 0

Figure 1: Waste Source Volume Distribution for Grout Disposal

Dilute wastes contained in tanks 241-AP-103, 241-AW-106, and 241-AW-102, as described in §2.1, were sampled and analyzed in support of Evaporator/Crystallizer operation. These materials are intended to be evaporated in 242-A Evaporator/Crystallizer Campaign 93-1 (O'Rourke 1992). As these materials are miscellaneous facilities wastes, and as the source streams are expected to be the generation source for such future wastes, process evaluation of the evaporated [i.e. concentrated] product has been conducted to estimate the composition and concentration of future concentrated wastes. As described by O'Rourke, expectations are that the concentrated materials would not be as highly concentrated as current DSSF material and would be classified as dilute-DSSF wastes (DDSSF). Such concentrated product is, as depicted in Figure 1, expected to constitute approximately 25 percent of all HGDP feed material.

Concentrated waste materials (DSSF) contained within tanks 241-AN-104 and 241-AN-105 were produced in Evaporator/Crystallizer campaigns 84-3, 84-5, and 85-3. These campaigns, and sample data in support of evaporator operation, are documented in Certa (1985), Gratny (1985), and Pontious (1986). Waste volumes, and their analyses, distributed to these tanks were used to estimate the composition of these wastes.

WHC-SD-WM-TI-528, Rev. 0

2.3 Wastes Described by Pretreatment Flowsheets

Wastes described in this document for which information gathered was from pretreatment flowsheets include the low-level streams resulting from pretreatment of Neutralized Current Acid Waste (NCAW), Neutralized Cladding Removal Waste (NCRW), Plutonium Finishing Plant (PFP) waste, and Complexed Concentrate (CC) waste.

NCAW is currently stored in tanks 241-AZ-101 and 241-AZ-102. NCRW is currently stored in tanks 241-AW-103 and 241-AW-105. PFP waste is currently stored in 241-SY-102 and in the PFP. CC waste is currently stored in DST and SST tanks 241-SY-101 and -103, 241-AX-102 and -103, and 241-AN-102 and -107 (Hanlon 1992).

These wastes and the low-level streams resulting from their pretreatment are described in Lowe (1991). These flowsheets include globally the existence and pretreatment of CC waste within the single-shell tanks (SST) 241-AX-102 and 241-AX-103. Although this document is prepared to describe the disposal of DST wastes only, the differences in waste volume and contents due to the small volume of these SST contents (151 kgal) upon the Lowe (1991) flowsheets are conservatively neglected in this document.

WHC-SD-WM-TI-528, Rev. 0

3.0 DATA HANDLING TECHNIQUES

As described in §2.0, above, three general forms of data were available for compilation and interpretation. In reiteration, these forms of data were actual sample data of existent tank wastes, sample and process data for wastes placed (or to be placed) into tanks, and process flowsheet estimates for future pretreatment residuals. The handling of each of these types of data are described below. Each of the data handling operations described below is depicted in Figure 2.

Key to the handling of data within the first two categories (data based upon direct sampling or evaporative processing of current and future wastes which will not be pretreated) is the knowledge that the sources for these wastes are common. Each of these wastes are the combined product of the miscellaneous low-level liquid wastes of Hanford's 100, 200, 300, and 400 Areas. Because the waste sources are similar they constitute a family which is herein described as the "DSSF Family" of wastes. Within this "family" the concentration of nonvolatile constituents is inversely proportional to water content. This familial relationship, as illustrated in Figure 3, is not perfect but allows data gaps to be bridged and the mean concentration of an analyte to be reasonably estimated in the absence of some data. As an example, if potassium concentrations are described for four of six tanks in the family, the mean of all six tanks is represented as the mean of the four tanks for which data is provided.

As will be described in §3.3, the conduct of pretreatment operations and the data provided do not allow handling of data in the manner of the DSSF family. This data is recognized to be incomplete, as not all analytes were followed through the flowsheets and because the differing nature of the sources do not allow one to make generalizations based on similarity of waste sources. In addition, proposed treatment regimes differ for the various waste streams. Thus, in totalizing expected waste streams from these operations, the mean of all waste streams was calculated as the weighted average of all streams. If no data was provided for an analyte in a stream, the weight assigned was zero while the volume of that stream remained a part of the calculation. This may introduce some non-conservative estimates for some analytes; however, it is believed that most analytes of potential concern in large streams are reported and form the basis of this family's estimate.

Summary tables for the work described in §§3.1 through 3.4 are contained in Tables 1-1 through 1-4 of the Appendix. All data are converted to units of $\mu\text{Ci/L}$ for radionuclides, and molarity for other constituents unless specifically noted. All radionuclide data are decayed to October 1, 1993, unless specifically noted; further discussion of decay is provided in §3.4.

Figure 3: Profile of DSSF Family Wastes Relative to Sodium

3.1 Data Handling for Existent Waste Samples

Two types of existent waste have been directly sampled for the purpose of characterization. These wastes are dilute non-complexed wastes and concentrated wastes. In all, these data describe the contents of six DSTs. Data flows shown in Figure 2 for such direct sampling are initiated with the symbol of a circle (O).

WHC-SD-WM-TI-528, Rev. 0**3.1.1 Existent Dilute Waste Sample Data**

Data described in this category includes sample data taken for dilute waste tanks 241-AP-103, 241-AW-106, and 241-AW-102. The sample constituent mean for these tanks was calculated as:

$$Mean_i = \frac{\sum_{j=1}^n [C_i]_j \times Volume_j}{\sum_{j=1}^n Volume_j} \quad [Eq. 3.1]$$

Where: [C] = constituent concentration,
 i = constituent identifier,
 j = sample, tank, or stream identifier,
 Volume_j is assigned a value of zero when [C]_i is unreported.

Tables 2-1, 2-2, and 2-3 of the Appendix contain the validated data for these dilute waste samples supporting O'Rourke (1992).

Tables 2-4, 2-5, and 2-6 of the Appendix contain the calculated summaries, by tank, of this analytical data. Appendix Table 1-1 contains a joint summary of these dilute wastes and includes an estimate of 241-AP-106 (Hendrickson and Welsh 1992a). These four tanks of dilute waste are used herein to describe future dilute waste receipts. Evaluation of expected evaporator operation for tanks 241-AP-103, 241-AW-106, and 241-AW-102 is calculated and displayed in Appendix Table 2-7 and included within Appendix Table 1-2; further discussion on this matter is provided in §3.2.2.

3.1.2 Existent Concentrated Waste Sample Data

Data described in this category includes sample mean data of concentrated waste tanks 241-AN-106 (Welsh 1991a), 241-AW-101 (Welsh 1991b), and 241-AN-103 (Hendrickson 1990). These data are incorporated in Appendix Tables 4-1 and 4-2. These tables do not embody any manipulation of the data other than unit conversion.

Particular aspects of the determination and use of the means for these tanks are embodied within the respective reference document, however, the following short summary is deemed appropriate.

Tank 241-AN-106 (Welsh 1991a) was sampled with the process knowledge that the tank was stratified into a high-phosphate concentration layer, a high-sulfate concentration layer, and at least one intermediate composition boundary layer. Twelve bottle-on-string samples of the waste were extracted and analyzed. Statistical analysis of the data indicated that the tank was indeed stratified and that the tank would be well represented by a stratified mean and sample deviation.

WHC-SD-WM-TI-528, Rev. 0

Tank 241-AW-101 (Welsh 1991b) was sampled with the expectation that the tank was relatively homogeneous. Twelve bottle-on-string samples were extracted and analyzed. Statistical analysis of the data indicated that the tank was homogeneous.

Tank 241-AN-103 (Hendrickson 1990) was sampled through core-drilling of the tank. The samples analyzed and reported were those of core composites.

3.2 Data Handling for Process History Samples

Both dilute and concentrated wastes are herein described by their evaporative process and analytical history. This category includes the dilute waste tank 241-AP-106, DSSF tanks 241-AP-105, 241-AN-104, and 241-AN-105, and future concentrated miscellaneous wastes. Data flows shown in Figure 2 for such evaporative process history and analysis are initiated with the symbol of a triangle (Δ).

3.2.1 Referenced Historical Process Analyses

As described in §2.2, the contents, in terms of expected mean concentrations, of tanks 241-AP-106 and 241-AP-105 were estimated in Hendrickson and Welsh (1992a and 1992b). Appendix Table 1-1, containing a joint estimate of dilute wastes, incorporates 241-AP-106 estimates. Appendix Table 4-2 contains waste tank 241-AP-105 estimates. Each are, again, converted to the common units of $\mu\text{Ci/L}$ and molarity except where noted.

3.2.2 Future Evaporator Product Estimation

The composition of concentrated miscellaneous wastes, as introduced in §§2.2 and 3.1.2, has been estimated to be represented by the evaporative product of tanks 241-AP-103, 241-AW-106, and 241-AW-102. Table 2-7 of the Appendix details the expected composite of these tanks and their boil-down. Non-volatile constituent concentrations are calculated as:

$$\text{Concentrated Mean}_i = \frac{\text{Non-Concentrated Mean}_i}{(1 - \text{WVR})} \quad [\text{Eq. 3.2}]$$

Where: WVR = $(1 - S/F)$ = Waste Volume Reduction factor (0.87),
 S = Slurry Volume (concentrated product),
 F = Feed Volume, and
 Non-Concentrated Mean_i is evaluated by Equation 3-1.

The 87% WVR used herein is that described by O'Rourke (1992) for expected Evaporator/Crystallizer operations. Thirty million liters (8×10^6 gallons) of this product, derived from Koreski and Strode (1992), are used in this estimate.

WHC-SD-WM-TI-528, Rev. 0

Volatile constituent concentrations (ammonia/ammonium and tritium) are calculated to be removed in the same ratio as water as:

$$\text{Concentrated Mean}_1 = \text{Non-Concentrated Mean}_1 \times \frac{\left(1 - \left(\frac{y_1}{z_1}\right) WVR\right)}{(1 - WVR)} \quad [\text{Eq. 3.3}]$$

Where: y_1 = molar density of pure water condensate (mol/L), and
 z_1 = molar density of water in feed (mol/L).

3.2.3 Process Analyses for Previous Evaporator Products

The current volumes of DSSF material contained within tanks 241-AN-104 and 241-AN-105 were generated in Evaporator campaigns 84-3, 84-5, and 85-3 (Certa 1985; Gratny 1985; and Pontious 1986).

A brief synopsis of transfer history, derived from operating records, relating to the generation sources of these materials is contained in Tables 2 and 3. Each of these tanks contained a small heel of dilute non-complexed waste or concentrated waste prior to the introduction of current materials.

TABLE 2: Tank 241-AN-104 Waste Source History			
Date	Activity	Volume (Kgal) Transferred	Tank Volume (Kgal) at Completion
Heel Present from Prior Activities			61
3/4/84	Evaporator Campaign 84-3 product to tank	290	351
4/84	Measured water loss	-3	348
9/84	Transfer to 3AN	-193	155*
10/5/84	Evaporator Campaign 84-5 product to tank	782	937
2/85	Measured water gain	3	940
4/6/85	Evaporator Campaign 85-3 product to tank	121	1,061

* Note: Shaded cells are those pertinent to calculations and analytical data.

WHC-SD-WM-TI-528, Rev. 0

TABLE 3: Tank 241-AN-105 Waste Source History			
Date	Activity	Volume (Kgal) Transferred	Tank Volume (Kgal) at Completion
Heel Present from Prior Activities			11
12/82	Evaporator Campaign 83-2 product to tank	259	270
1/83	Evaporator Campaign 83-4 product to tank	369	639
3/84	Transfer	-30	609
3/84	Transfer from 4AN	499	1,108
2/85	Transfer to Evaporator	-954	154
3/85	Evaporator Campaign 85-3 product to tank	239*	393
4/85	Evaporator Campaign 85-3 product to tank	732	1,125

* Note: Shaded cells are those pertinent to calculations and analytical data.

For purposes of this estimation, the existent volumes were assumed to be the represented by the materials introduced. This is considered a reasonable approximation. Upon inspection of Table 2 one should observe that only 5% of the current contents of 241-AN-104 consist of materials present prior to the data applied. Similarly, approximately 14% of material present in 241-AN-105 was previously present; this material was dilute-DSSF.

Evaporator campaign 84-3, 84-5, and 85-3 data are presented in Appendix Tables 3-1, 3-2, and 3-3. Calculations upon this data are summarized on Appendix Tables 3-4 and 3-5, which include the decay of radioisotopes to the date of October 1, 1993. The method and selection basis for this decay date are described in §3.4, below.

WHC-SD-WM-TI-528, Rev. 0

The contents of tanks 241-AN-104 and 241-AN-105 are described in relation to analytical data supporting the above evaporator campaigns and the volumes received. Material transfers and minor discrepancies between transfer records and campaign post-run documentation result in the application of the following volumes (kgal) of materials in the estimation of material concentrations:

<u>Evaporator Campaign</u>	<u>241-AN-104 Contribution</u>	<u>241-AN-105 Contribution</u>
84-3	148.5	0
84-5	790	0
85-3	121	971

Thus, the analyses supporting the above volumes generated are weighted by volume to calculate the mean contents of these tanks in the manner of Equation 3-1. The resulting estimations for these tanks are contained in Appendix Table 4-3, decayed to the latest date of the above samples (April 1985).

3.3 Data Handling for Pretreatment Low-Level Streams

At this time it is believed that Lowe (1991), provides the most complete and current estimate of material balances for pretreatment streams. Lowe's flowsheets are a function of what is currently known about NCAW, NCRW, CC, and PFP wastes and how they are currently planned to be pretreated. The pretreatment regimens are intended to separate a low volume of high level and transuranic material for deep geologic disposal from a large volume of low-level waste for near-surface disposal. The separation technology development and implementation is, admittedly, far from complete and subject to political, public perception, and funding variances. With this in mind, Lowe's flowsheets have been assigned an impact and quality assurance level consonant to no external review. As such, data used in this document are directly (some unit conversions) from this reference as no comparable data source exists. Should it become necessary to guide and require further pretreatment, the acceptance criteria for wastes embodied in Hendrickson (1991b) must be enforced prior to acceptance of wastes for disposal.

As described in §3.0, an assumption that the mean of all these waste streams would be represented by a mean of those reported is not considered appropriate. The reasons for this are that the original sources of the waste differ, and because the wastes would undergo differing treatment regimes. Table 1-4 of the Appendix details the data from Lowe (1991) and the evaluation of a mean as that described in Equation 3-1 with no volume weights assigned to zero.

In reiteration, this may introduce some non-conservative estimates for some analytes; however, it is believed that most analytes of potential concern in large streams are reported and form a valid basis of this family's estimate. The two lowest volume streams comprising 0.37% of the pretreated volumes to the HGDG are least well described by Lowe (1991); lack of explicit data on all aspects of these streams is considered insignificant.

WHC-SD-WM-TI-528, Rev. 0

3.4 Data Summarization and Interpretation

Data handling in §§3.1 through 3.3, above, resulted in the development of:

- a) An estimate of the composition of dilute wastes to be received [Appendix Table 1-1],
- b) An estimate of concentrated material to be produced in the future [Appendix Table 2-7],
- c) Estimates of all currently available concentrated feed [Appendix Tables 4-1, 4-2, and 4-3], and
- d) An estimate of all expected materials subject to pretreatment [Appendix Table 1-4].

In order to combine the above information and to determine an estimate of the overall inventory of materials to be received at the disposal facility, several aspects of process and data handling must be considered. These aspects include decay dates for radioactive materials, evaluation of requirements for dilute wastes, use and application of limiting values, and analytical errors. Each of these aspects and their impact on the estimate of overall inventory are described below.

3.4.1 Application of Uniform Decay Date

In order to combine analytical data on the radionuclide content of existent waste streams, a uniform decay date was selected. Unlike chemical constituents which will not significantly vary over time except through physical means, the radioactive components of the wastes continue to decrease in concentration through radioactive decay. The decay date chosen for this document has been that of October 1, 1993. This date has been chosen as it is the currently expected date of HGDG startup.

An example of the use and necessity of a uniform decay date in these calculations may be provided by describing the decay of ^{137}Cs in four existent concentrated waste tanks: 241-AN-103 and -106, 241-AW-101, and 241-AP-105. The analytical data is described within the Appendix tables as:

Tank	Sample Decay Date	^{137}Cs ($\mu\text{Ci/L}$)	Days before 10/01/93
241-AN-103	12/15/84	7.50 E+05	3,212
241-AP-105	01/30/89	2.85 E+05	1,705
241-AN-106	04/21/89	2.05 E+05	1,631
241-AW-101	07/17/90	5.20 E+05	1,172

The half-life of ^{137}Cs used within this document is 30.17 years (see Appendix Table 5-1 for other radionuclide data used). Conversion factors of 86,400 seconds per day and 31,556,736 seconds per sidereal year are used within decay

WHC-SD-WM-TI-528, Rev. 0

equations (Hendrickson 1991a) to determine the activity of remaining material at some given time as:

$$Activity(t) = Activity(t_0) e^{\left(\frac{-\lambda t}{t_{1/2}}\right)} \quad [Eq. 3.4]$$

where: t = interval of decay, seconds
 λ = decay constant [$\ln(2) = 0.693$], and
 $t_{1/2}$ = isotope half-life, s.

For 241-AN-103 data, the uniform date activity may be evaluated as:

$$Activity(t) = 7.5 E+05 e^{\left(\frac{-0.693 \cdot \left(3,212 \text{ days} \cdot \frac{86,400 \text{ s}}{\text{day}}\right)}{30.17 \text{ year} \cdot \left(\frac{31,556,736 \text{ s}}{\text{year}}\right)}\right)} \left(\frac{\mu Ci}{L}\right)$$

$$= 6.128 E+05 \left(\frac{\mu Ci}{L}\right) \quad [Eq. 3.5]$$

In this manner, the decayed activities of ^{137}Cs are calculated as:

Tank	^{137}Cs Activity ($\mu\text{Ci/L}$)	
	Sample Data	Decayed Data to 10/01/93
241-AN-103	7.50 E+05	6.13 E+05
241-AP-105	2.85 E+05	2.56 E+05
241-AN-106	2.05 E+05	1.85 E+05
241-AW-101	5.20 E+05	4.83 E+05

In this fashion, and with the half-lives described in Appendix Table 5-1, all data which can be decayed are so calculated. Materials to be generated in the future are not decayed and are so marked.

3.4.2 Evaluation of Dilute Waste Requirements

Current waste acceptance criteria limit the radiolytic heat content of wastes to be disposed to the HGD. Radiolytic heat loading is a calculation of the heat released to the waste through high energy decay. Limits on such heat loading have been established to adequately protect the disposal system and product grout from excessive temperature during and after operational activities.

The unit established for the evaluation of heat loading of grout waste feeds is the heat provided by the decay of one curie of ^{137}Cs and its metastable daughter $^{137\text{m}}\text{Ba}$ [$^{137\text{m}}\text{CsBa}$]. Other high energy decay chains, of those expected

WHC-SD-WM-TI-528, Rev. 0

in the wastes, are prorated and summed as described in Hendrickson (1991a) to yield a decay heat evaluation in terms of ^{137}Cs heat equivalents. The limiting acceptance value for radiolytic heat loading has been established as 0.3718 Ci ^{137}Cs heat equivalents/L (Hendrickson 1991b) at the time of disposal.

Observation of radiolytic heat loading of existent wastes [Appendix Table 1-3] calculated in this fashion, following decay as described in §3.4.1, demonstrates that some wastes would exceed the heat loading limit if disposed in their current form and concentration. Specifically, wastes contained in DST waste tanks 241-AW-101, 241-AN-103, -104, and -105 are each anticipated to exceed the heat loading limit. As such, these wastes must be blended with dilute wastes to reduce the overall radiolytic heat load.

Appendix Table 1-3 calculations yield the volumetric feed fraction (%) at which these wastes may be blended with dilute wastes to yield a mixture at the heat loading limit. Direct calculations of required dilute waste volume and their summation result in the determination that approximately nine million liters (2.39×10^6 gallons) of dilute waste are required. The composition of these dilute wastes are discussed in §§2.1 and 2.2 and tabulated in Appendix Table 1-1. The volume and composition of these required dilute wastes are carried throughout subsequent calculations.

3.4.3 Use and Application of Limiting Values

All laboratory analyses have some limit of detection and quantitation. When the concentration of a constituent is below the limit of the method, the analytical value typically reported is the detection or quantitation limit value. Such data is tagged as a "less-than" value. Examples of such "less-than" results are contained within Appendix Tables 2-1 through 2-6 and 3-1 through 3-5. Where such "less-than" data are used within this document, they are acted upon and weighed with other analyses as if they were indeed real values.

This application of limiting values of detection and quantitation as real values is inherently conservative and has the unfortunate side effect of eliminating any estimate of analytical variability (e.g. see Welsh 1991a and 1991b). Thus, despite this shortfall in general statistical validity, it is considered the only reasonable way to handle this data directly while developing generalized inventory estimates.

In keeping with the application of "less-than" values as real values, summary tables (Table 4 and Appendix Tables 1-1, 1-2, 1-4 and 4-1 through 4-3) of this document no longer carry the "less-than" indicators. As is applied in §4.0, the existence and validity of the use of "less-than" values for a constituent may be investigated when the waste constituent is of significant importance.

WHC-SD-WM-TI-528, Rev. 0

3.4.4 Analytical Errors

Data used within this evaluation include a broad range of qualified and unqualified data. Errors inherent within any analytical report include those of sampling error as well as random and systematic measurement error.

Analytical summaries, such as those prepared for waste tanks 241-AN-106 and 241-AW-101 (Welsh 1991a and 1991b) have addressed the lack of significant effect of sampling error upon well characterized tanks when those tanks are considered homogenous. In this perspective, reported mean concentrations are considered adequate and often carry standard deviations of approximately 10% to 17%. The overall variance is composed of both sampling and measurement error.

For many data sources used within this document, it is not possible at this time to easily determine whether such analyses were conducted in duplicate, nor whether blanks, matrix spikes and other qualification methods were employed in data generation. Thus, the only available estimates of error on such reports are those of analytical measurement error.

The overall analytical measurement error is composed of two variance components. The first is known as the systematic error variance (S_s^2) and the second is the random error variance (S_r^2). The combined estimate of variance is:

$$S^2 = S_s^2 + \frac{S_r^2}{n} \quad [Eq. 3.6]$$

where n is the number of measurements used to estimate the concentration (the analytical measurement). The systematic error variance is usually estimated through the use of known standards. Examples of laboratory standard errors include percent standard deviations (one standard deviation) of 10.96% for ^{99}Tc at an activity near 2 $\mu\text{Ci/L}$ and 17.16% for ^{129}I at an activity near 1 $\mu\text{Ci/L}$. For Westinghouse Hanford Company the laboratory standard results are reported and stored in the LMCS database. The random error variance is usually estimated from the duplicate sample results.

Estimates of these errors, in terms of standard deviation or relative standard deviation, have been computed based on analytical results from samples obtained from Tanks 241-SY-101, 241-AN-106, and 241-AW-101 (Herting et al. 1992; Welsh 1991a and 1992b). Standard deviation is the square root of the variance. The error estimates based on Tank 241-SY-101 sample data (Window E) are found in Tables 7.5, 7.6, and 7.10 in Herting et al. (1992). Although not directly specified, the magnitude of the random error component based on sample data from Tank 241-AN-106, can be obtained from the percent difference data (%Diff.) given in Appendix C of Welsh (1991a). The random error estimates based on Tank 241-AW-101 are found in Table 4 of Welsh (1991b).

WHC-SD-WM-TI-528, Rev. 0

For those analytes which are reported as "less than" values, the random analytical error can also be estimated from the analysis of laboratory standards.

The overall tank concentration error is a function of the analytical measurement error and the "degree" of homogeneity within the tank. If the tank is homogeneous, then the overall error is mainly comprised of the analytical error. The random variability within Tank 241-AW-101, which is estimated by the relative standard deviation [RSD] (standard deviation divided by the mean multiplied by 100), can be computed from Table 6 of Welsh (1991b). However, the random error (in terms of RSD) for the overall mean would be the $RSD/\sqrt{n}$. The random variability within Tank 241-AN-106, which is estimated by the relative standard deviation, can be computed from Table 6 of Welsh (1991a). The random error (in terms of RSD) for the overall mean would be the $RSD/\sqrt{n}$. Tank 241-AN-106 is known to be a stratified tank (not homogenous). Thus the within tank variability should be larger than the within tank variability of Tank 241-AW-101.

Overall analytical errors described above are expected to yield standard deviations about data in the region of 10% to 20%. Although sensitivity analyses may apply such error ranges about data in evaluating the environmental impact of waste constituents in the disposal action, the evaluation of a best estimate of overall inventory precludes direct application within this document.

3.4.5 Data Summary

The two basic groups of wastes, the "DSSF Family" and pretreatment family, remain substantially different in source and handling. Thus, the combination of these materials in this evaluation is conducted as the last action.

3.4.5.1 DSSF Family Waste Summary

The DSSF Family waste contribution to the HGDP waste feed projections is a combination of existent concentrated wastes, future concentrated wastes, and dilute wastes. The combination of these materials may be gathered and easily expressed.

Armed with the estimate of diluent waste volume required (§3.4.2), the DSSF family of wastes is collected on Appendix Table 1-2. This table shows the translation from the previous calculations of waste composition, such that each existent concentrated waste is decayed to the uniform decay date of October 1, 1993, by applying Equation 3.4. Dilute wastes and future concentrated wastes are not decayed. A summary of the DSSF family is calculated and presented on Appendix Table 1-2 in the manner of Equation 3.1. This summary is passed forward and presented as the first data column of Table 4.

WHC-SD-WM-TI-528, Rev. 0

3.4.5.2 Grout Waste Feed Projection Summary

A final combination of DSSF family wastes and pretreated wastes is performed in the method of Equation 3.1. Just as the dilute and future concentrated wastes were not decayed to form Appendix Table 1-2, above, pretreated waste composition is not decayed. This is not considered a significant error in that the time of generation of these wastes is not yet known, and as the pretreatment regimes through which this material will pass are expected to remove the majority of intermediate-lived radionuclides (e.g. ¹³⁷Cesium) and may remove a majority of the long-lived transuranic material.

The resultant composition estimate is provided in Table 4. It must be noted that the third data column (Total Feed) of Table 4 is equivalent to that concentration for an analyte if that analyte is described in only one of the major streams. This is considered a conservative yet necessary assumption when no analysis for the analyte is available.

Certain radionuclides are considered sensitive enough, from a long-term release standpoint, that refinement or affirmation of an estimate contained in Table 4 is warranted. These "special estimates" are described in §4.0 and yield Table 8 which overrides some estimates described in Table 4.

3.5 Recommendations on Data Usage

It is recommended that the information provided herein, when used in summary form, be segmented by the two waste families described. As described in §3.3, fewer analytes are described for two low volume pretreatment streams, errors introduced from the lack of completeness of the preliminary pretreatment flowsheets is not expected to be significant with regard to these low volume streams.

It is recommended that more complete data be developed to accurately estimate the projected volume and concentration profile of future wastes, and that information provided herein as estimates be replaced with actual sample data when such becomes available. Of particular note, high ²⁴¹Americium data reported for Evaporator campaign 84-3, if representative, may prohibit (Hendrickson 1991b) the disposal of the DSSF wastes in tanks 241-AN-104 and 241-AN-105 without pretreatment.

Information acquisition on these, and other, tank wastes is often complicated by extensive safety precautions. Such precautions, and the development of documentation for such, may effectively prohibit significant information acquisition on these wastes in the near future.

Speciated organic chemical analysis has not been within the analytical compass of the majority of wastes described in this document, and as such, has been omitted herein. Although not described in this document, such analysis must be conducted to ensure that waste feeds remain acceptable for disposal (Hendrickson 1991b).

WHC-SD-WM-TI-528, Rev. 0

With the above considerations, the estimates provided within this document are considered to be the most current and complete estimate of waste feed materials to the Hanford Grout Disposal Program and may be used as a guide in regulatory compliance, general flowsheet, and performance assessment activities wherein an order of magnitude accuracy is required. This document, as it describes an average of the inherent differences between waste streams should not be construed to override single stream data for safety analyses or design especially when new data on each waste stream is acquired.

WHC-SD-WM-TI-528, Rev. 0

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 0

TABLE 4: Grout Treatment Facility Waste Projection
 (Units: $\mu\text{Ci/L}$ for radionuclides,
 molarity for others unless noted)

Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Ag	8.90 E-05	4.08 E-05	6.48 E-05
Al	4.92 E-01	4.05 E-01	4.48 E-01
As	2.00 E-04	1.97 E-04	1.99 E-04
B		3.37 E-03	3.37 E-03
Ba	4.66 E-05	1.18 E-04	8.22 E-05
Be	1.78 E-03		1.78 E-03
Bi	3.13 E-04		3.13 E-04
Ca	4.24 E-04	7.30 E-03	3.87 E-03
Cd	6.45 E-05	1.60 E-04	1.12 E-04
Ce		1.44 E-04	1.44 E-04
Cr	4.23 E-03	1.92 E-02	1.18 E-02
Cu	1.49 E-04	4.08 E-04	2.79 E-04
Fe	1.78 E-03	1.85 E-02	1.01 E-02
Hg	5.49 E-06		5.49 E-06
K	3.44 E-01	5.65 E-02	2.00 E-01
La		1.15 E-04	1.15 E-04
Li		6.81 E-05	6.81 E-05
Mg	1.61 E-03	4.05 E-03	2.83 E-03
Mn	2.62 E-04	7.03 E-03	3.66 E-03
Mo	4.24 E-04	8.54 E-04	6.40 E-04
Na	6.00 E+00	5.00 E+00	5.50 E+00

Decay Date = 10/01/93

3-17

WHC-SD-WM-TI-528, Rev. 0

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Nd		1.20 E-04	1.20 E-04
Ni	6.22 E-04	1.89 E-03	1.26 E-03
P	4.98 E-02		4.98 E-02
Pb	5.37 E-04	1.19 E-04	3.27 E-04
Sb	1.31 E-03	6.13 E-05	6.86 E-04
Se	1.75 E-04	6.13 E-04	3.95 E-04
Si	3.38 E-03	8.77 E-03	6.08 E-03
Ta	1.36 E-05		1.36 E-05
Ti	9.14 E-05	9.95 E-05	9.55 E-05
U (g/L)	1.37 E-03	4.24 E-01	2.13 E-01
V	3.14 E-04		3.14 E-04
W	1.13 E-03		1.13 E-03
Zn	1.66 E-03	4.08 E-04	1.03 E-03
Zr	2.50 E-04	5.09 E-02	2.56 E-02
CN ⁻	4.01 E-04		4.01 E-04
NH ₃	2.03 E-02	3.99 E-03	1.21 E-02
CO ₃ ⁻²	2.12 E-01	1.12 E-02	1.11 E-01
Cl ⁻	1.15 E-01	5.51 E-02	8.48 E-02
F ⁻	1.03 E+00	3.95 E-01	7.14 E-01
SO ₄ ⁻²	7.63 E-02	6.70 E-02	7.16 E-02
NO ₃ ⁻	1.72 E+00	3.76 E+00	2.74 E+00

Decay Date = 10/01/93

3-18

WHC-SD-WM-TI-528, Rev. 0

TABLE 4: Grout Treatment Facility Waste Projection
 (Units: $\mu\text{Ci/L}$ for radionuclides,
 molarity for others unless noted)

Waste Component	DSSF Family	Pretreated Wastes	Total Feed
NO_2^-	9.37 E-01	7.42 E-02	5.04 E-01
PO_4^{-3}	2.69 E-02	3.46 E-02	3.07 E-02
OH^-	2.15 E+00	1.55 E-01	1.15 E+00
TOC (g/L)	8.15 E+00	3.54 E-03	4.07 E+00
TIC (g/L)	5.19 E+00		5.19 E+00
SPG	1.29 E+00		
pH	1.35 E+01		
^3H	5.07 E+00		5.07 E+00
^{14}C	2.85 E-01	3.71 E+00	2.00 E+00
^{60}Co	3.91 E+01	1.56 E+01	2.73 E+01
^{63}Ni		1.19 E+02	1.19 E+02
^{79}Se	3.03 E+00		3.03 E+00
^{90}Sr	1.82 E+03	2.39 E+04	1.29 E+04
^{94}Nb	4.33 E+01		4.33 E+01
^{95}Nb	5.34 E+01	3.49 E+03	1.78 E+03
^{99}Tc	4.87 E+01	5.47 E+01	5.17 E+01
^{103}Ru	1.29 E+02		1.29 E+02
$^{106}\text{RuRh}$	1.62 E+03	2.07 E+03	1.84 E+03
^{113}Sn	1.78 E+02		1.78 E+02
^{129}I	2.18 E-01	2.61 E-02	1.22 E-01
^{134}Cs	5.77 E+02	6.21 E+01	3.19 E+02

Decay Date = 10/01/93

3-19

WHC-SD-WM-TI-528, Rev. 0

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
^{137}Cs	2.27 E+05	3.67 E+04	1.32 E+05
$^{144}\text{CePr}$	9.80 E+02	2.12 E+03	1.55 E+03
^{154}Eu	2.51 E+02	4.79 E+01	1.49 E+02
^{155}Eu	2.85 E+02	4.91 E+01	1.67 E+02
^{226}Ra	1.32 E+03		1.32 E+03
^{234}U	3.37 E-01		3.37 E-01
^{235}U	1.97 E-02		1.97 E-02
^{238}U	7.94 E-02		7.94 E-02
^{237}Np	8.81 E-01	2.90 E-04	4.39 E-01
^{238}Pu	2.23 E-01	9.41 E-02	1.59 E-01
$^{239/240}\text{Pu}$	2.09 E+00	3.08 E+00	2.59 E+00
^{241}Am	1.35 E+03	2.78 E+01	6.86 E+02
^{243}Cm	4.14 E-02		4.14 E-02
^{244}Cm	8.92 E-02	1.65 E-02	5.28 E-02
TB	1.56 E+04		1.56 E+04
AT	1.86 E+00		1.86 E+00
Volume (L)	6.08 E+07	6.12 E+07	1.220 E+08

Decay Date = 10/01/93
3-20

WHC-SD-WM-TI-528, Rev. 0

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Additional analytes described for pretreated wastes			
^{95}Zr		1.73 E+03	1.73 E+03
^{125}Sb		5.41 E+02	5.41 E+02
^{152}Eu		4.08 E+00	4.08 E+00
^{241}Pu		8.90 E+00	8.90 E+00
^{242}Pu		1.57 E-05	1.57 E-05

Decay Date = 10/01/93
3-21

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 0

4.0 SPECIAL ESTIMATES OF CRITICAL ISOTOPES

As described in §3.5, it is recommended that further analytical data be developed for the projection of grout waste estimates. Such additional data will not come rapidly nor inexpensively. In the meantime, however, waste material estimates derived above may either overestimate, underestimate or fail to address waste constituents critical to an assessment of the human and environmental protection afforded by the proposed disposal action (Performance Assessment).

In consideration of this, one may turn to methods other than direct waste analysis in order to evaluate whether such an assessment should consider application of constituent concentrations differing from those described in Table 4.

The purpose of this section is to consider, describe, and apply other methods of waste constituent estimation and to provide recommendations regarding waste constituents currently believed to be potentially critical in evaluation of the proposed disposal action. Sections 4.1 through 4.10 develop estimates and recommendations for waste constituents including ^{241}Am , ^{238}U , ^{237}Np , ^{230}Th , ^{226}Ra , ^{135}Cs , ^{129}I , ^{126}Sn , ^{99}Tc , ^{94}Nb , ^{79}Se , and ^{14}C . Section 4.11 summarizes and tabulates these estimates and recommendations.

Although it may be expected that ^{137}Cs and ^{90}Sr will play a major role in the assessment of disposal actions, estimates based on other than analytical data are not pursued in this section because these materials are routine waste analytes; as such, it is considered inappropriate to override analytical measurements with mathematical estimates.

4.1 $^{135}\text{Cesium}$ Estimation

Cesium-135 is not a routine analyte in waste analyses and is not represented in Table 4. The reasons for this are several and include incapability to chemically separate ^{135}Cs from ^{134}Cs and ^{137}Cs and a half-life five orders-of-magnitude [OM] greater than that of ^{137}Cs and six OM greater than that of ^{134}Cs .

The approach used herein to estimate ^{135}Cs content of wastes to be received at the HGDP is to apply data from the burnup of fuel with results in the form of ^{135}Cs and ^{137}Cs content from which a ratio of production may be made.

Hedengren (1985, 1986) and Hedengren and Goldberg (1987) have conducted calculations using the ORIGEN2 code to determine expectations of fission, actinide, cladding, and activation products from the irradiation of fuel under various conditions. Table 5 contains excerpts of data from these references as they apply to calculations within §4. of this document. The product data of Table 5 derive from ORIGEN2 runs assuming a 12% (^{240}Pu /total Pu) product using mixed Mark IV (80%) and Mark IA (20%) N Reactor fuel. Some benchmarking of ORIGEN2 for N reactor operations has been conducted but the code has not

WHC-SD-WM-TI-528, Rev. 0

completed verification and validation. Despite the unvalidated status of this code, it and its results are used within this document as they are expected to be approximately correct and because they provide the only reasonable nonclassified production estimate available at this time.

TABLE 5: ORIGEN2 Yield Per Metric Ton of Fuel (Ci) [For 12% Pu Mixed Mark IV and Mark IA Fuel Five Years After Discharge]				
Isotope	Fuel Fission Product	Fuel Actinide Product	Cladding and Fuel Activation Product	Specific Activity (Ci/g)
¹⁴ C	1.024 E-05		2.023 E-02	4.46 E+00
⁷⁹ Se	3.757 E-02			6.96 E-02
⁹⁴ Nb	9.158 E-06		6.093 E-08	1.90 E-01
⁹⁹ Tc	1.259 E+00		1.736 E-06	1.70 E-02
¹²⁶ Sn	6.490 E-02			2.84 E-02
¹²⁹ I	2.709 E-03			1.76 E-04
¹³⁵ Cs	3.356 E-02			1.15 E-03
¹³⁷ Cs	8.184 E+03			8.65 E+01
²²⁶ Ra (W)		6.150 E-10		9.89 E-01
²³⁰ Th		1.697 E-05		2.06 E-02
²³⁷ Np		2.213 E-02		7.05 E-04
²³⁸ U		2.656 E-01		3.36 E-07
²⁴¹ Am		4.243 E+01		3.43 E+00
²⁴¹ Pu		4.509 E+03		1.03 E+02

Note: Specific Activities derived from Walker et al. (1989). ²²⁶Ra production in terms of watts (W).

As can be seen in Table 5, 0.03356 Ci of ¹³⁵Cs is produced for every 8,184 Ci of ¹³⁷Cs. Similar production ratios of other materials will be applied below.

WHC-SD-WM-TI-528, Rev. 0

4.1.1 Back-Decay of ^{137}Cs Data

In order to apply the relative data given above, an estimate for ^{137}Cs is required. The estimate of cesium-137 production can be calculated from analysis at any date after production given the half-life of the material. Thus, where Table 1-2 of the Appendix contains ^{137}Cs data decayed to October 1, 1993, each of these analyses may be back-decayed to an estimated time of material separation.

For purposes of uniformity, the time of fuel discharge is assumed to be October 1, 1977, and fuel processed in PUREX on October 1, 1982. This period of five years between fuel discharge and processing (fuel "cooling" period) is assumed to be a slightly conservative and typical interval necessary in these and later calculations involving the ingrowth of radioisotopes. Fuel cooling periods of five years have been assumed in subsequent calculations to compensate for the ingrowth of radioactive isotopes; these may be significant when the parent radionuclide is present in high concentration in the irradiated fuel (e.g. ^{230}Th ingrowth from alpha decay of ^{234}U).

Although not all of the wastes described here were processed, sampled, or concentrated by the above dates, they provide a reasonable average fuel discharge date, and consequent initial generation and decay of cesium-137. Applying a half-life of 30.17 years and a decay time of -11 years to the ^{137}Cs data on Appendix Table 1-2 results in cesium activities, at that time, of 20.7 million curies. Details of this calculation are provided in Table 6, below.

It should be noted that close agreement between ^{137}Cs estimates may be found between that provided above and through the Integrated Data Base (DOE 1991 [Table 2-17]) (IDB). Back-decay of IDB data to October 1982 would yield ^{137}Cs activity in tanks to be 21.1×10^6 Ci.

4.1.2 ^{135}Cs Cesium Production

The estimate of ^{135}Cs production may be made as the ORIGEN2 ratio of ^{135}Cs production to ^{137}Cs production times the analytical estimate of production five years after discharge of ^{137}Cs and computed as:

$$\begin{aligned} \text{Cs-135 (Ci)} &= \frac{0.03356 \text{ Ci Cs-135}}{8,184 \text{ Ci Cs-137}} * 20,663,000 \text{ Ci Cs-137} \quad [\text{Eq. 4.1}] \\ &= 84.73 \text{ Ci Cs-135} \end{aligned}$$

For the purposes of the Performance Assessment, correction of this activity through decay to current values is insignificant (>99.9996% remaining in 1993) and thereby neglected.

WHC-SD-WM-TI-528, Rev. 0

TABLE 6: Waste ¹³⁷ Cs Activity [Decay Date 10/1/1982]			
Tank	Cs-137 (Ci/L)	Volume (L)	Cs-137 (Ci)
106-AN	0.238	3,667,985	874,094
101-AW	0.622	3,826,969	2,378,645
105-AP	0.329	3,145,609	1,035,247
104-AN	0.973	3,024,479	2,941,880
105-AN	0.649	4,269,852	2,772,392
103-AN	0.789	3,546,854	2,798,393
Future DDSSF	0.156	30,282,640	4,713,889
Dilutes	0.02863	9,045,989	259,014
Pretreated	0.0472	61,164,750	2,889,253
Total		121,975,126	20,662,806

4.1.3 ¹³⁵Cesium Estimate Usage

The estimate of ¹³⁵Cs production given above as 84.7 Ci is greater than the reported current activity of 59.2 Ci within the IDB (DOE 1991 [Table 2-17]). Waste content of ¹³⁵Cs is not described within the HDW-EIS. At this time, no information has been identified which would suggest that ¹³⁵Cs has been preferentially separated from ¹³⁷Cs in any Site operations (chemically identical); thus reduction of either of these two estimates by any referencable factor is not reasonable.

In reference to the two estimates derived or given above, it is recommended that grouted waste inventory calculations use a base case not exceeding a maximum ¹³⁵Cs concentration applying the ORIGEN2 and analytically derived estimate of 0.695 μ Ci/L. Sensitivity analyses may be pursued of 0.485 μ Ci/L corresponding to IDB estimates of site inventory.

4.2 ²³⁷Neptunium Estimation

An improved estimate of ²³⁷Np is sought in this section due to the minimal data provided in reference information. Further complicating this estimate is the ingrowth of ²³⁷Np from the alpha decay of ²⁴¹Am. This ingrowth is not explicitly incorporated in the transport and dose codes to be used in performance assessments, but the input may be manipulated to account for the ingrowth of the americium as its half-life is only 432.7 years compared to the neptunium half-life of 2.14 million years.

WHC-SD-WM-TI-528, Rev. 0

4.2.1 Revision of ^{241}Am Estimates

The americium contained within the waste streams is the result of neutron bombardment of fuel and the ingrowth from beta-decay of ^{241}Pu . Under the conditions of burnup described in §4.1, Hedengren and Goldberg (1987, page 117), provide a five year post-discharge yield of 42.43 Ci ^{241}Am per metric ton of fuel. Using a calculation in the form of Equation 4.1, ^{241}Am content of wastes decayed to October 1993, would be 105,256 Ci. The IDB estimate of ^{241}Am in all Hanford Double-Shell wastes decayed to October 1993 is 52,253 Ci (DOE 1991).

The difficulty remains with estimation of realistic activities of the wastes. As can be seen in Appendix Tables 3-1 through 3-5, 4-3, and 1-2, the overall "DSSF Family" americium estimate of Table 4 is driven by one sample analysis from Evaporator Campaign 84-3 (Certa 1985). If this analytical value of 11,400 $\mu\text{Ci/L}$ accurately represents both tanks 241-AN-104 and 241-AN-105, the americium content of these tanks would be 83,155 Ci; clearly this activity, in excess of IDB estimates, is not reasonable. If the analytical value represented only that portion of 241-AN-104 which has above been attributed from Campaign 84-3, this portion of material would include 6,408 Ci of ^{241}Am . This is a possible, but not highly realistic value.

Omitting the analytical americium datum of Campaign 84-3, no data is available to consider for DSSF tanks 241-AN-104 and 241-AN-105. In the overall manner of this document, the preferred method of estimation should be that of bridging a data gap. Data may be bridged in this instance by choosing a maxima or by interpolation based upon other parameters, such as is depicted in Figure 3 of §3.0. Data does remain for other DSSF wastes, and may form a basis for revising the estimate.

4.2.1.1 TRU Limitation in DSSF Waste

Waste feeds to the HGDP are limited by regulatory requirements to a maximum of 100 nanocuries of transuranic (TRU) material per gram of waste (Hendrickson 1991b). Given the density of wastes contained within tanks 241-AN-104 and 241-AN-105, a maximum ^{241}Am concentration within these wastes is 153 $\mu\text{Ci/L}$. Use of such a concentration is acceptable as a bounding value as these wastes would require pretreatment for TRU removal were they any higher. The use of this concentration is a factor of almost seventy-five below the analytically reported values (see §4.2.1 and Appendix Table 1-2) of other DSSF wastes.

A summary of the estimate of overall ^{241}Am to be received by the HGDP under the assumption that 241-AN-104 and -105 are at their TRU limits is contained in Table 7. These sources are ranked by expected contribution. It should be noted that the volumes described in Table 7 do not exactly equal those of Table 6 as no americium estimate for NCAW pretreatment streams 13 are provided in Lowe (1991); differences due to these small volume streams (0.37% of pretreatment volumes) are neglected in further calculations of this section.

WHC-SD-WM-TI-528, Rev. 0

TABLE 7: ²⁴¹Americium Sources [Decay Date 10/01/82]

Source	Am-241 (Ci/L)	Volume (L)	Am-241 (Ci)	Mean (Ci/L)
NCAW 2AZ	3.20 E-04	3.50 E+06	1,118.53	
DSSF (4AN/5AN Max.)	1.53 E-04	7.29 E+06	1,114.99	
PFP	1.76 E-04	2.08 E+06	366.29	
CC	3.05 E-06	3.90 E+07	119.08	
NCAW 1AZ	3.39 E-05	3.49 E+06	118.28	
DDSSF	8.96 E-07	3.03 E+07	27.14	
DSS/DSSF (not 4AN/5AN)	1.37 E-06	1.42 E+07	19.37	
NCRW 5AW	8.63 E-07	5.30 E+06	4.57	
Dilutes	1.04 E-07	9.05 E+06	0.94	
NCRW 3AW	9.96 E-08	7.57 E+06	0.75	
Total		1.22 E+08	2,889.94	2.374 E-05
Decayed to 10/01/93				2.33 E-05

Note: This assumes that tanks 241-AN-104 and -105 are bounded in ²⁴¹Am content at 100 nCi/g. NCAW 2AZ concentration believed to be erroneously high.

Relative contributions of ²⁴¹Am from projected waste feeds for this assumption are depicted in Figure 4. This image emphasizes the expectation that the vast majority (>98%) of ²⁴¹Am to be received in HGDP wastes is to be contained in pretreated waste streams and assumed maxima within DSSF tanks 241-AN-104 and 241-AN-105. Such an estimate, in conjunction with the impacts of near-surface disposal of this material, may be the basis for extended pretreatment to remove additional transuranic material.

4.2.1.2 Concentration Factor Evaluation in DSSF Waste

Although a conservative bound for ²⁴¹Am content may be found in §4.2.1.1, it is possible to use the observations depicted in Figure 3 to arrive at an estimate of ²⁴¹Am content in tanks 241-AN-104 and -105. Those concentrated waste tanks for which reasonable americium data are available include tanks 241-AN-106, 241-AW-101, 241-AN-103, and an estimate based on processing of 241-AP-105. The temporary exclusion of dilute, future concentrate, and pretreated wastes is necessary for this estimate as will be evident below.

WHC-SD-WM-TI-528, Rev. 0

Figure 4: Distribution of Am-241 Sources to Grout (Assumes maximum allowable in 4AN/5AN)

Back-decay of ^{241}Am data for these four concentrated waste tanks to 1982 and comparing these data to waste sodium content, in the manner of Figure 3, provides a linear regression characterized by Equation 4.2 with a correlation coefficient of nearly 92%. This is considered a good fit and may allow global estimation of ^{241}Am content based upon sodium content. Applying waste volumes and sodium concentrations of the existent concentrated DSSF family wastes, one arrives at a weighted mean sodium molarity of 9.87 mol/L.

$$\text{Am-241 } (\mu\text{Ci/L}) = 0.13867 * \text{Na (M)} + 0.16508 \quad [\text{Eq. 4.2}]$$

Applying this sodium concentration to Equation 4.2 yields a mean estimate of 1.533 $\mu\text{Ci } ^{241}\text{Am/L}$ for these 21.48 million liters (32.93 Ci). Continued calculation in the manner of Table 7 results in an overall estimated concentration of 14.4 $\mu\text{Ci/L}$.

As described above, dilute and future concentrate wastes were not considered in the linear regression. The basis of this exclusion is that analytical data

WHC-SD-WM-TI-528, Rev. 0

on those wastes do not support the above regression; in fact, Equation 4.2 would predict approximately twice as much americium than has been analytically reported in the dilute wastes.

It is postulated that previous americium and cesium sources in the waste streams to the DSTs have slowly decreased in content of these materials with serial facility shutdowns. In this respect, the analytical estimates for dilute and future concentrates as described above will be conservative.

Pretreated waste streams should not follow Equation 4.2 as it is the express intent of such pretreatment to remove transuranic material. Thus, the flowsheets (Lowe 1991) continue to provide the appropriate estimation basis for these wastes.

4.2.1.3 Usage of ^{241}Am Estimates

Revised estimates of americium content of HGDP waste feeds in §§4.2.1.1 have resulted in an expectation of a mean ^{241}Am content of $23.32 \mu\text{Ci/L}$ [decay date 10/01/93] over all wastes. This estimate is recommended as a base case when applying such data. Three sensitivity case evaluations, each decayed to 10/01/93, of americium content beyond the base case are most well supported as:

- Case I: Linear regression of americium data relative to sodium content (Eq. 4-2) to describe existent concentrated DSSF Family wastes while using remainder of base case; $1,757.9 \text{ Ci}$ ($14.4 \mu\text{Ci/L}$), and
- Case II: IDB basis; $52,253 \text{ Ci}$ ($428.4 \mu\text{Ci/L}$).
- Case III: Production and decay, related to waste ^{137}Cs content [analogous to Eq. 4.1] for DSSF Family wastes plus pretreated waste estimate; $105,256 \text{ Ci}$ ($863 \mu\text{Ci/L}$).

A case for estimation based on IDB less that pretreated material to be shipped to the Hanford Waste Vittrification Project is untenable as the pretreatment flowsheet estimates (Lowe 1991) of material fed to pretreatment exceed ^{241}Am estimates of the IDB by greater than one OM. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated $17,000 \text{ Ci}$ of ^{241}Am in near-surface barriered disposal; this activity, in view of the span of the above cases, is sufficiently close to those cases that establishment of an another case for this estimate is not considered necessary.

4.2.2 Revision of ^{237}Np Estimates

As described above, the neptunium contained within the waste streams is the result of bombardment of fuel (^{235}U $\rightarrow$ ^{236}U $\rightarrow$ ^{237}U $\rightarrow$ ^{237}Np) and the ingrowth from decay of ^{241}Pu and ^{241}Am . Under the conditions of burnup described in §4.1, Hedengren and Goldberg (1987, pages I15 and I17), provide yields of $4,509 \text{ Ci}$ ^{241}Pu (43.78 g), 42.43 Ci ^{241}Am (12.38 g), and 0.02213 Ci ^{237}Np (31.40 g) per metric ton of fuel five years after discharge.

WHC-SD-WM-TI-528, Rev. 0

4.2.2.1 Production Estimation of ^{237}Np

As described above, it is obvious that a calculation in the form of Equation 4.1 and subsequent decay would yield an inordinately large estimate of the neptunium and americium decay daughters of the plutonium. More simply, this type of relationship would not be appropriate as the plutonium has been extracted in fuel processing. Fractional retention of ^{241}Pu in the waste stream yields a negligible difference in the ^{237}Np content as a result of decay, thus an approximation of complete ^{241}Pu removal in fuel processing may be used. In the manner of Equation 4.1, a production estimate of ^{237}Np would be 55.87 Ci which, with additional decay from ^{241}Am (assuming 100% yield of ^{237}Np), would yield a 1993 estimate of 55.88 Ci ^{237}Np .

4.2.2.2 Usage of ^{237}Np Estimates

A revised estimate, based on production, of neptunium content of HGDW waste feeds in §4.2.2.1, would result in the expectation of a mean ^{237}Np content of 0.458 $\mu\text{Ci/L}$. The IDB estimate of 45.1 Ci, would yield a mean of 0.37 μCi $^{237}\text{Np/L}$. As presented in Table 4, an analytically based estimate of content would be 53.6 Ci with a mean concentration of 0.439 $\mu\text{Ci/L}$.

It is recommended that the base case of waste evaluation, when such is applied in long term dose assessments, remain that provided in Table 4. Two sensitivity cases, one of lower activity and one higher, may be supported with the IDB estimate and the expected production (§4.2.2.1) estimate, respectively. As each of these sensitivity cases is within a factor of two of the recommended base case, it is noted that inaccuracies or differences in transport modeling may obviate any long term dose sensitivity due to such a minor variance in waste activity.

4.3 ^{226}Ra Estimation

Radium-226 is produced within irradiated fuel and is a daughter of $^{230}\text{thorium}$. Its radioactive daughters follow the decay chain of $^{226}\text{Ra} \rightarrow ^{222}\text{Rn} \rightarrow ^{218}\text{Po} \rightarrow ^{214}\text{Pb} \rightarrow ^{214}\text{Bi} \rightarrow ^{214}\text{Po} \rightarrow ^{210}\text{Pb} \rightarrow ^{210}\text{Bi} \rightarrow ^{210}\text{Po} \rightarrow ^{206}\text{Pb}$ (stable), where the decays between, and following, radon and lead-210 are rapid. Lead-210 is unstable but has a much greater half-life than the intermediate daughters. A better estimate of the content of ^{226}Ra in the waste is required as significant quantities of ^{226}Ra may result in large dose consequences due to the decay of it and its daughters over the period of the Performance Assessment.

The estimate of ^{226}Ra given in Table 4 is derived from analyses of current dilute waste tanks (see §3.1.1). Data reported from these wastes are "less-than" values (see Appendix Tables 2-1 through 2-6) resulting in an extrapolated DSSF Family concentration of 1,325 $\mu\text{Ci/L}$. Such an estimate would indicate expected disposal of 80,551 Ci of ^{226}Ra in DSSF Family wastes. This large estimate is not consistent with the absence of discussion of this isotope within the IDB and the HDW-EIS.

WHC-SD-WM-TI-528, Rev. 0

Lacking any other analytical data on this isotope, the waste content may again be approximated in the manner of §4.1.2, based upon production. Hedengren and Goldberg (1987) encompass the production of ^{226}Ra within fuel irradiation. However, due to the necessity to limit the publication of what was felt to be extraneous data (many zeros would be displayed and printed in the document if a limiter had not been applied) ^{226}Ra data is only displayed within tables of thermal power rather than directly in tables of mass or activity. Table 19 (Hedengren and Goldberg 1987, page 120) provides the thermal power of ^{226}Ra five years after discharge to be 6.15×10^{-10} watts. Browne et al. (1986) provide the delta of the alpha decay of ^{226}Ra to ^{222}Rn to be approximately 4.77 Mev/dis. Thus, the thermal power at that time may be calculated in terms of activity as:

$$Q\left(\frac{\text{W}}{\text{Ci}}\right) = \frac{4.77 \text{ Mev}}{\text{dis}} \times \frac{1.60219\text{E-}06 \text{ erg}}{\text{Mev}} \times \frac{1\text{E-}07 \text{ Ws}}{\text{erg}} \times \left(\frac{3.70\text{E+}10 \text{ dis}}{\text{s}} \right) \left[\text{Eq. 4.3} \right]$$

$$= 2.8277\text{E-}02 \left(\frac{\text{W}}{\text{Ci}} \right)$$

$$\text{Ra-226} \left(\frac{\text{Ci}}{\text{tonne}} \right) = \left(\frac{\frac{6.15\text{E-}10 \text{ W}}{\text{tonne}}}{\frac{2.828\text{E-}02 \text{ W}}{\text{Ci}}} \right) = 2.175 \text{E-}08 \left(\frac{\text{Ci}}{\text{tonne}} \right) \quad [\text{Eq. 4.4}]$$

$$\text{Ra-226 (Ci)} = \frac{2.175\text{E-}08 \text{ Ci Ra-226}}{8,184 \text{ Ci Cs-137}} * 140,280,000 \text{ Ci Cs-137} \quad [\text{Eq. 4.5}]$$

$$= 3.73 \text{E-}04 \text{ Ci Ra-226}$$

Note that the ^{137}Cs value of Equation 4.5 is not that developed for and used in Equation 4.1. This higher ^{137}Cs number is derived from two sources in addition to that activity described in Table 6. The use of this higher value is in part due to the acknowledgement that lack of data on pretreatment flowsheets does not indicate the absence of a waste component. Explicitly, waste sources have or will have ^{137}Cs removed from the streams in processes which do not effect the removal of other analytes.

Pretreated waste streams may be corrected for ^{137}Cs content as an 11 year back-decayed ^{137}Cs estimate of material fed to pretreatment operations (Lowe 1991), thereby replacing the pretreated activity of 2.25 million curies of Table 6 with 46.41 million curies.

Both pretreated wastes and general DST contents may be corrected due to cesium scavenging in B Plant operations based upon cesium capsule content. This type

WHC-SD-WM-TI-528, Rev. 0

of correction recognizes that material separated from the product capsules was returned to single- and double-shell tanks. Current ^{137}Cs capsule content is described within the IDB (DOE 1991) as 59.2 million curies decayed to December 31, 1991. Back-decaying this activity to October 1, 1982 yields an activity of 73.21 million curies. Lacking determinate data on the destination of specific fractions of these byproduct liquids, it is herein assumed that the target analyte produced during the production of 73 million Ci of ^{137}Cs has been entirely transferred into materials destined for near-surface disposal.

Open literature discussion of pertinent aspects of chemistry and chemical separations of cladding and fuel are provided by Cotton (1989), Hodgson et al. (1985), Swanson (1988), and GE (1955).

Thus, use of a summation of 140.28 million Ci value assumes that the target isotope of this calculation is entirely deposited in grout waste.

This estimate of a total content of 3.73×10^{-4} Ci of ^{226}Ra is 9 OM lower than the estimate guided by the analytical values reported. One must note, however, that the analytical values reported were "less-than" values and were reported as the detection limit for this isotope. In the above regards, the recommended base case estimate for this isotope is 3.06×10^{-6} $\mu\text{Ci/L}$, corresponding to the ORIGEN2 calculation as applied above. A calculated ^{230}Th parent concentration of 2.38×10^{-3} $\mu\text{Ci/L}$ should be included in the base case for further ingrowth of ^{226}Ra . With no further information available, no sensitivity cases are recommended.

Although caution may be advisable in the ORIGEN2 based estimate of ^{226}Ra , should ORIGEN2 errors result in actual activities several OM greater than described, it is expected that such activities will remain of little consequence in long term dose assessment.

4.4 ^{129}I Iodine Estimation

Iodine-129 is a fission product within irradiated fuel. Its presence within the waste feed is of potential concern due to its greater than 15 million year half-life and expected mobility in soil systems.

Several estimates may be made of expectations of ^{129}I concentration within grout feed wastes. The IDB (DOE 1991 [Table 2-17]) estimates site inventory to be 0.265 Ci. Calculations resulting in iodine concentrations described in Table 4 would indicate that a total of 14.8 Ci ^{129}I would be disposed. Calculation in the form of Equation 4.5, using ORIGEN2 (Hedengren 1985 [Case I, page 134]), would indicate production of 46.4 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) indicated an expectation of no more than 34 Ci to be placed in near-surface disposal.

Although it would obviously be beneficial to demonstrate that IDB estimates of site inventory limit ^{129}I disposition in grout wastes, the magnitude of investigation required to substantiate such is not within the scope of this

WHC-SD-WM-TI-528, Rev. 0

of correction recognizes that material separated from the product capsules was returned to single- and double-shell tanks. Current ^{137}Cs capsule content is described within the IDB (DOE 1991) as 59.2 million curies decayed to December 31, 1991. Back-decaying this activity to October 1, 1982 yields an activity of 73.21 million curies. Lacking determinate data on the destination of specific fractions of these byproduct liquids, it is herein assumed that the target analyte produced during the production of 73 million Ci of ^{137}Cs has been entirely transferred into materials destined for near-surface disposal.

Open literature discussion of pertinent aspects of chemistry and chemical separations of cladding and fuel are provided by Cotton (1989), Hodgson et al. (1985), Swanson (1988), and GE (1955).

Thus, use of a summation of 140.28 million Ci value assumes that the target isotope of this calculation is entirely deposited in grout waste.

This estimate of a total content of 3.73×10^{-4} Ci of ^{226}Ra is 9 OM lower than the estimate guided by the analytical values reported. One must note, however, that the analytical values reported were "less-than" values and were reported as the detection limit for this isotope. In the above regards, the recommended base case estimate for this isotope is 3.06×10^{-6} $\mu\text{Ci/L}$, corresponding to the ORIGEN2 calculation as applied above. A calculated ^{230}Th parent concentration of 2.38×10^{-3} $\mu\text{Ci/L}$ should be included in the base case for further ingrowth of ^{226}Ra . With no further information available, no sensitivity cases are recommended.

Although caution may be advisable in the ORIGEN2 based estimate of ^{226}Ra , should ORIGEN2 errors result in actual activities several OM greater than described, it is expected that such activities will remain of little consequence in long term dose assessment.

4.4 ^{129}I Iodine Estimation

Iodine-129 is a fission product within irradiated fuel. Its presence within the waste feed is of potential concern due to its greater than 15 million year half-life and expected mobility in soil systems.

Several estimates may be made of expectations of ^{129}I concentration within grout feed wastes. The IDB (DOE 1991 [Table 2-17]) estimates site inventory to be 0.265 Ci. Calculations resulting in iodine concentrations described in Table 4 would indicate that a total of 14.8 Ci ^{129}I would be disposed. Calculation in the form of Equation 4.5, using ORIGEN2 (Hedengren 1985 [Case I, page I34]), would indicate production of 46.4 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) indicated an expectation of no more than 34 Ci to be placed in near-surface disposal.

Although it would obviously be beneficial to demonstrate that IDB estimates of site inventory limit ^{129}I disposition in grout wastes, the magnitude of investigation required to substantiate such is not within the scope of this

WHC-SD-WM-TI-528, Rev. 0

document. Further, as this case is one wherein the disposal inventory would be much smaller than the next lowest estimate, the application of any of the other expressed estimates would bound such an impact analysis.

It is recommended that the base case of waste evaluation be that provided in Table 4 of $0.122 \mu\text{Ci/L}$. Two sensitivity cases based upon ORIGEN2 and the HDW-EIS are supportable with estimates of $0.381 \mu\text{Ci/L}$ and $0.279 \mu\text{Ci/L}$, respectively.

4.5 ^{126}Sn Estimation

Tin-126 is a fission product within irradiated fuel. Its presence within the waste feed is of potential concern due to its 100,000 year half-life and the very short half-life (12.4 days) of its radioactive daughter ^{126}Sb .

^{126}Sn is not a typical analyte and is not described within Table 4 or the HDW-EIS. The IDB (DOE 1991 [Table 2.17]) describes a tank inventory of 104 Ci. Calculation in the manner of Equation 4.5 yields an estimate of 1,112 Ci based upon ORIGEN2 data (Hedengren 1985 [Case I, page I33]).

The recommended base case in long term dose assessment is that of waste concentrations of $9.12 \mu\text{Ci/L}$ based upon production. A sensitivity case is available as $0.853 \mu\text{Ci/L}$ based upon IDB inventory but is not highly recommended.

4.6 ^{99}Tc Estimation

Technetium-99 is primarily generated as a fission product in irradiated fuel and in activated cladding associated with irradiated fuel. In addition, it is generated from the decay of ^{99}Mo . For the purposes of this document and reality, complete molybdenum-99 decay occurs during fuel cooling. ^{99}Tc is again a concern in long term performance assessment due to its half-life of 213,000 years and potential mobility.

Table 4 estimates of ^{99}Tc disposal total to 6,311 Ci. The IDB (DOE 1991 [Table 2.17]) describes tank inventories of 13,300 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) envisioned near-surface disposal of 19,000 Ci. Production estimates based upon Equation 4.5 yield 21,581 Ci. Technetium as an activation product has been neglected from the above calculations as the fission production outweighs activation by 6 OM (Hedengren 1985 and 1986).

In view of the proximity of Table 4 estimates (based upon waste analyses) to production and pretreatment estimates, the recommended base case for waste evaluation is that described in Table 4 of $51.74 \mu\text{Ci/L}$. Sensitivity cases for evaluation would be those of production at $176.9 \mu\text{Ci/L}$ and of IDB inventory at $109 \mu\text{Ci/L}$.

WHC-SD-WM-TI-528, Rev. 0

4.7 ⁹⁴Niobium Estimation

Niobium-94 present within irradiated fuel, cladding, and resultant waste is primarily generated by neutron activation of ⁹³Nb (stable) and fission. ⁹⁴Nb retains a half-life of 20,000 years. A better estimate of waste content of this isotope is required due to its relatively long half-life, calculated concentrations (Table 4), and possible waste zone intrusion.

Table 4 DSSF Family estimates of ⁹⁴Nb are 43.3 μ Ci/L (2,634 Ci in that volume). Thorough research of ⁹⁴Nb data reported from these wastes indicates that these data are "less-than" values (see Appendix Tables 3-1 through 3-5 and 4-1 through 4-3 and their references). No information is provided in Lowe (1991) on niobium-94 concentrations, however, application of Equation 4.5 provides an ORIGEN2 fission and activation production of 0.158 Ci. This small estimate of ⁹⁴Nb may be the reason that this material is not described within either the IDB (DOE 1991) or the HDW-EIS (DOE 1987).

It is recommended that the base case of waste evaluation be that provided by production as a mean concentration of 1.30×10^{-3} μ Ci/L. This case considers analytical data (including "less-thans") and the relatively negligible production estimate described above. As no further information is available for consideration at this time, no sensitivity case is recommended in waste evaluation.

4.8 ⁷⁹Selenium Estimation

Selenium-79, with a half-life of 65,000 years, is generated by fission. A better estimate of waste content of this isotope is required due to its relative mobility and possible waste zone intrusion.

Table 4 DSSF Family estimates of ⁷⁹Se are 3.03 μ Ci/L (185 Ci in that volume). No information is provided in Lowe (1991) on selenium-79 concentrations, however, application in the form of Equation 4.5 provides an ORIGEN2 production (Hedengren 1985 [page 126]) estimate of 644 Ci. IDB (DOE 1991 [Table 2.17]) estimates of ⁷⁹Se in tanks total 65.8 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated the placement of 260 Ci of ⁷⁹Se in near-surface disposal.

The recommended base case of waste evaluation is that described by Table 4 estimates of 3.03 μ Ci/L. This base case is greater than possible sensitivity cases of 0.54 μ Ci/L and 2.13 μ Ci/L based upon the IDB and HDW-EIS, respectively, and lower than a sensitivity case of 5.28 μ Ci/L based upon production.

4.9 ¹⁴Carbon Estimation

Carbon-14 present within irradiated fuel, cladding, and resultant waste is primarily generated by neutron activation of natural carbon (¹²C and ¹³C) present in fuel and cladding as impurities. ¹⁴C retains a half-life of 5,730

WHC-SD-WM-TI-528, Rev. 0

years. A better estimate of waste content of this isotope is required due to its expected concentrations (Table 4), and possible waste zone intrusion.

Table 4 estimates of ^{14}C including both analytical support for DSSF Family wastes and pretreatment projections yield waste expectations of $2.00\ \mu\text{Ci/L}$ (244 Ci in total volume). Applications of Equation 4.5 yield fission and activation product (Hedengren 1985 and 1986) expectations of 347 Ci of ^{14}C in the waste to be received. IDB (DOE 1991) estimates of ^{14}C in tanks total 569 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated the placement of 2,300 Ci of ^{14}C in near-surface disposal.

Because of the analytical support provided for Table 4 estimates, the recommended base case for waste evaluation remains that of Table 4. Sensitivity cases available for evaluation are suggested based on production and the IDB at concentrations of $2.84\ \mu\text{Ci/L}$ and $4.66\ \mu\text{Ci/L}$, respectively.

4.10 ^{238}U Uranium Estimation

Uranium-238 is present within irradiated and non-irradiated fuel due to its abundance of approximately 99.1%. ^{238}U has a half-life of approximately 4.5×10^9 years and undergoes alpha and beta decay along the pathway $^{238}\text{U} \rightarrow ^{234}\text{Th} \rightarrow ^{234}\text{Pa} \rightarrow ^{234}\text{U} \rightarrow ^{230}\text{Th}$. Decay of ^{230}Th is described in §4.3, above. Due to the long-term impact of this decay chain of long-lived materials leading to a short-lived gaseous daughter, a better estimate of this material is sought.

Table 4 DSSF Family estimates of ^{238}U , based solely on analysis of tank 241-AN-103 and dilute evaporator feeds, result in expectations that 4.8 Ci would be disposed with these wastes. Lowe (1991) does not describe estimates of ^{238}U in feed materials to pretreatment operations. The IDB describes an estimate of 0.945 Ci (~2,800 kg) present in tank wastes. The HDW-EIS anticipated 20 Ci to be placed in near-surface disposal. Although a substantially larger amount of ^{238}U has been handled with the processing of irradiated fuel, IDB and HDW-EIS estimates are imbedded with an assumption of 99% extraction of uranium and plutonium from irradiated fuel (GE 1955). For this reason, production estimates may not be made in the manner of §4.1.2.

Although only limited analytical data supports ^{238}U estimates in the vicinity of that described by the IDB, the recommended base case for waste evaluation is that of the analytical concentrations in DSSF Family wastes ($0.079\ \mu\text{Ci/L}$). A suggested sensitivity case is that of the IDB at $7.75 \times 10^{-3}\ \mu\text{Ci/L}$. At this time no sensitivity case is suggested which would entail the OM increase anticipated in the HDW-EIS.

WHC-SD-WM-TI-528, Rev. 0

4.11 Special Estimate Summary

Table 8, below, contains a summary of recommendations for base case and sensitivity case waste evaluations developed in §§4.2 through 4.10. As supported by the individual development of these special estimates, the constituent concentrations of these recommended base and sensitivity case estimates should replace or amend those displayed in Table 4 when such is used in the evaluation of the waste or proposed disposal action. Described above, the use of IDB and HDW-EIS estimates are not recommended within this document as they have not been subjected to a comprehensive review nor have their predictions been verified against actual sample data; as such, any such use may only be considered for sensitivity cases.

WHC-SD-WM-TI-528, Rev. 0

TABLE 8: Special Estimates of Critical Isotopes				
Isotope	Recommended Base Case Waste Concentration ($\mu\text{Ci/L}$)	Recommendation Basis	Sensitivity Case Concentrations ($\mu\text{Ci/L}$) and Bases	
^{241}Am	23.3	Waste Analysis/ Limited 4AN/5AN	14	Waste Analysis/Linear Regression 4AN/5AN
			440	IDB
			860	Production ²
^{238}U	0.08	Waste Analysis	0.01	IDB
^{237}Np	0.44	Waste Analysis	0.37	IDB
			0.46	Production
^{230}Th	2.4 E-03	Production	None	
^{226}Ra	3 E-06	Production	None	
^{135}Cs	0.69	Production	0.49	IDB
^{129}I	0.12	Waste Analysis	0.38	Production
			0.28	HDW-EIS
^{126}Sn	9.1	Production	0.85	IDB
^{99}Tc	51.7	Waste Analysis	180	Production
			110	IDB
^{94}Nb	1.3 E-03	Production	None	
^{79}Se	3.0	Waste Analysis	0.5	IDB
			2.1	HDW-EIS
			5.3	Production
^{14}C	2.0	Waste Analysis	2.8	Production
			4.7	IDB

2

Production [=] Application of ORIGEN2 data to waste ^{137}Cs content.

WHC-SD-WM-TI-528, Rev. 0

5.0 REFERENCES

- Browne, E., R. B. Firestone and V. S. Shirley, Table of the Radioactive Isotopes, John Wiley & Sons, New York, NY, 1986.
- Certa, P. J., 1985, "242-A Evaporator/Crystallizer FY 84 Campaign Run 84-3 Post Run Document," SD-WM-PE-018, April 30, 1985.
- Cotton, F. Albert, and G. Wilkinson, 1989, *Advanced Inorganic Chemistry, Fifth Edition*, John Wiley & Sons, New York, NY, 1989.
- DOE, 1987, *Final Environmental Impact Statement, Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington*, DOE/EIS-0113, U. S. Department of Energy, December 1987.
- DOE, 1988, "Record of Decision," Federal Register, 53 FR 12449, April 14, 1988.
- DOE, 1991, *Integrated Data Base for 1991: U. S. Spent Fuel and Radioactive Waste Inventories, Projections, and Characteristics*, DOE/RW-0006, Revision 7, October 1991, U. S. Department of Energy, Washington, D. C.
- GE, 1955, *PUREX Technical Manual*, HW-31000DEL, General Electric Company, Richland, WA, March 25, 1955. Publicly released August 6, 1992.
- Gratny, E. G., 1985, "242-A Evaporator/Crystallizer FY'84 Campaign 84-5 Post Run Document," SD-WM-PE-022, September 4, 1985.
- Hanlon, B. M., 1992, "Tank Farm Surveillance and Waste Status Summary Report for February 1992," WHC-EP-0182-47, May 1992.
- Hedengren, D. C., 1985, "ORIGEN2 Predictions of N Reactor Fuel Fission Product Composition," SD-CP-TI-077, Revision 0, March 14, 1985.
- Hedengren, D. C., 1986, "ORIGEN2 Predictions of N Reactor Cladding and Fuel Activation Product Composition," SD-CP-TI-094, Revision 0, November 11, 1986.
- Hedengren, D. C., and H. J. Goldberg, 1987, "ORIGEN2 Predictions of N Reactor Fuel Actinide Composition," SD-CP-TI-105, Revision 1, August 4, 1987.
- Hendrickson, D. W., 1990, "Methods and Data for Use in Determining Source Terms for the Grout Disposal Program," SD-WM-TI-355, Revision 1, March 22, 1990.
- Hendrickson, D. W., 1991a, "Radiolytic Heat Loading Calculation Methods for the Hanford Grout Disposal Facility," WHC-SD-WM-TI-455, Revision 0, January 2, 1991.

WHC-SD-WM-TI-528, Rev. 0

- Hendrickson, D. W., 1991b, "Grout Treatment Facility Waste Feed Acceptance Criteria," WHC-SD-WM-RD-019, Revision 1, October 18, 1991.
- Hendrickson, D. W. and T. L. Welsh, 1992a, "Tank 241-AP-106 Sampling and Characterization Plan," WHC-SD-WM-TP-117, Revision 0, January 30, 1992.
- Hendrickson, D. W. and T. L. Welsh, 1992b, "Tank 241-AP-105 Sampling and Characterization Plan," WHC-SD-WM-TP-130, Revision 0, April 16, 1992.
- Herting, D. L., D. B. Bechtold, B. E. Hey, B. D. Keele, L. Jensen, and T. L. Welsh, 1992, "Laboratory Characterization of Samples Taken in December 1991 (Window E) From Hanford Waste Tank 241-SY-101," WHC-SD-WM-DTR-026, Revision 0, August 20, 1992.
- Hodgson, K. M., D. L. Herting, W. W. Schultz, L. A. Bray, and J. L. Swanson, 1985, "Content and Removal of TRU Elements from Aqueous Zirconium Cladding Waste," *Proceedings of the International Symposium on Actinide/Lanthanide Separations, Honolulu, Hawaii, USA, 16-22 December 1984*, World Scientific, 1985.
- Koreski, G. M., and J. N. Strode, 1992, "Operational Waste Volume Projections," SD-WM-ER-029, Revision 16, October 28, 1992.
- Lowe, S. S., 1991, "Preliminary Material Balances for Pretreatment of NCAW, NCRW, PFP and CC Wastes," WHC-SD-WM-TI-492, Revision 0, September 10, 1991.
- O'Rourke, J. F., 1992, "Process Control Plan for 242-A Evaporator Campaign 93-1," WHC-SD-WM-PCP-008, Revision 0, November 24, 1992.
- Pontious, N. L., 1986, "242-A Evaporator/Crystallizer FY 1985 Campaign 85-3 Post-Run Document," SD-WM-PE-023, Revision 0, February 24, 1986.
- Swanson, J. L., 1988, *Recent Studies Related to Head-End Fuel Processing at the Hanford PUREX Plant*, PNL-6609, Battelle Pacific Northwest Laboratory, Richland, WA, August 1988.
- Walker, F. W., J. R. Parrington, F. Feiner, 1989, *Nuclides and Isotopes*, 14th ed., General Electric Company, San Jose, CA, 1989.
- Welsh, T. L., 1991a, "Tank 241-AN-106 Characterization Results," WHC-SD-CP-TP-065, Revision 0, March 8, 1991.
- Welsh, T. L., 1991b, "Tank 241-AW-101 Characterization Results," WHC-SD-WM-TRP-055, Revision 0, December 19, 1991.

APPENDIX

WHC-SD-WM-TI-528, Rev. 0

THIS PAGE INTENTIONALLY LEFT BLANK

A-ii

WHC-SD-WM-TI-528, Rev. 0

GROUT TREATMENT FACILITY WASTE FEED PROJECTIONS

Waste Analyses and Calculations

TABLE

	<u>Page</u>
1-1: Dilute Waste Summary	A-3
1-2: DSSF Family Waste Summary	A-6
1-3: DSSF Family Radiolytic Heat Loading	A-10
1-4: Pretreatment Waste Summary	A-11
2-1: 241-AP-103 Validated Analysis Data	A-14
2-2: 241-AW-106 Validated Analysis Data	A-18
2-3: 241-AW-102 Validated Analysis Data	A-22
2-3: 241-AW-102 Validated Analysis Data - cont.	A-26
2-4: 241-AP-103 Analysis Summary	A-30
2-5: 241-AW-106 Analysis Summary	A-33
2-6: 241-AW-102 Analysis Summary	A-36
2-7: Future Dilute DSSF Waste Summary	A-39
3-1: Evaporator Campaign 84-3 Analysis Data	A-43
3-2: Evaporator Campaign 84-5 Analysis Data	A-46
3-3: Evaporator Campaign 85-3 Analysis Data	A-49
3-4: Evaporator Campaign 84-5 Analysis Summary	A-52
3-5: Evaporator Campaign 85-3 Analysis Summary	A-55
4-1: Concentrated Waste Summary Data - 101AW, 103AN	A-58
4-2: Concentrated Waste Summary Data - 105AP, 106AN	A-61
4-3: Concentrated Waste Summary Data - 104AN, 105AN	A-64
5-1: Radioisotope Decay Data	A-67

FIGURE

	<u>Page</u>
Figure A-1: Grout Feed Material Data Flowsheet.	A-1

WHC-SD-WM-TI-528, Rev. 0

THIS PAGE INTENTIONALLY LEFT BLANK

A-iv

WHC-SD-WM-TI-528, Rev. 0

Figure A-1: Grout Feed Material Data Flowsheet.

Figure A-1, comparable to Figure 2 of this document, provides the schematic of data flow used in the calculation of inventory estimates of Sections 1.0 through 4.0. Table references provided in Figure A-1 are correlated with the index to this Appendix and will allow one to follow calculations where necessary.

Radiolytic decay dates are as noted on each table.

WHC-SD-WM-TI-528, Rev. 0

THIS PAGE INTENTIONALLY LEFT BLANK

TABLE 1-1: Dilute Waste Summary

Dilute Waste Analyses and Estimates								
Units: Molarity; uCi/L for radionuclides; others as noted								
	Analytical Results			Estimate	Analytical		Overall Dilute	
Component	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
Ag	3.71e-07	4.46e-05	8.27e-06	3.15e-05	9.23e-06	2.36e-05	1.64e-05	2.05e-05
Al	9.12e-03	6.21e-02	1.81e-02	1.07e-01	1.95e-02	2.84e-02	4.76e-02	4.50e-02
As	6.44e-07	3.50e-05	2.01e-05	1.37e-08	1.30e-05	1.72e-05	8.85e-06	1.69e-05
B								
Ba	4.73e-07	1.26e-05	9.47e-06	6.98e-06	5.72e-06	6.28e-06	6.13e-06	5.14e-06
Be								
Bi				5.91e-05			5.91e-05	
Cs				8.48e-05			2.73e-05	
Cd	9.85e-07	2.64e-05	3.56e-06	1.10e-06	5.27e-06	1.40e-05	3.93e-06	1.23e-05
Ce								
Cr	7.10e-05	4.41e-04	2.05e-04	3.17e-04	1.73e-04	1.87e-04	2.19e-04	1.58e-04
Cu				3.89e-05			3.89e-05	
Fe	1.49e-05	1.34e-03	5.65e-04	8.12e-05	4.10e-04	6.63e-04	3.04e-04	6.09e-04
Hg	1.03e-08	5.21e-08	2.49e-08	8.22e-08	2.16e-08	2.12e-08	4.11e-08	3.17e-08
K				1.11e-01			1.11e-01	
La								
Li								
Mg	2.97e-05	4.36e-04	5.53e-04	2.20e-04	2.97e-04	2.75e-04	2.73e-04	2.32e-04
Mn	4.74e-07	1.22e-04	1.77e-05	4.87e-05	2.30e-05	6.60e-05	3.13e-05	5.39e-05
Mo				6.12e-05			6.12e-05	
Na	2.31e-01	1.73e+00	7.30e-01	1.08e+00	6.27e-01	7.63e-01	7.71e-01	6.29e-01
Nd								
Ni				1.75e-04			1.75e-04	
P				2.26e-03			2.26e-03	
Pb	1.93e-06	2.11e-04	3.86e-05	1.49e-04	4.35e-05	1.11e-04	7.75e-05	9.67e-05
Pd								
Sb								
Se	1.05e-07	1.04e-07	6.33e-08	4.30e-08	8.77e-08	2.38e-08	7.33e-08	3.08e-08
Si				4.40e-04			4.40e-04	
Sn								
Te				1.88e-05			1.88e-05	
Ti				1.01e-05			1.01e-05	
U g/L			1.54e-08	2.27e-02	1.18e-08		7.29e-03	1.60e-02

WHC-SD-WM-TI-528, Rev. 0
TABLE 1-1 continued.

Dilute Waste Analyses and Estimates								
Units: Molarity; uCi/L for radionuclides; others as noted								
	Analytical Results			Estimate	Analytical		Overall Dilute	
Component	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
V								
W								
Zn	4.19e-06	1.59e-03	1.40e-04	5.04e-04	2.60e-04	8.77e-04	3.39e-04	7.17e-04
Zr				5.65e-05			5.65e-05	
CN-	2.29e-05	7.63e-05	4.93e-05	1.07e-04	4.06e-05	2.67e-05	6.19e-05	3.60e-05
S-2								
NH4 +	2.75e-03	3.29e-03	1.03e-02	4.97e-04	5.95e-03	4.23e-03	4.20e-03	4.25e-03
NH3								
CO3-2				2.06e-02			2.06e-02	
Cl-	1.40e-03	1.51e-02	1.31e-02	1.51e-02	1.36e-02	7.41e-03	1.41e-02	6.59e-03
F-	6.81e-03	3.43e-01	2.12e-01	4.12e-04	2.29e-01	1.69e-01	1.56e-01	1.67e-01
SO4-2	3.65e-03	3.56e-02	2.43e-02	1.15e-03	1.62e-02	1.62e-02	1.14e-02	1.66e-02
NO3-	6.41e-02	5.79e-01	2.28e-01	1.55e-01	1.97e-01	2.63e-01	1.83e-01	2.25e-01
NO2-	2.82e-02	2.08e-01	5.59e-02	1.12e-01	6.24e-02	9.69e-02	7.83e-02	7.94e-02
PO4-3	1.45e-03	7.67e-03	1.84e-03	2.28e-03	2.40e-03	3.49e-03	2.36e-03	2.93e-03
OH-	8.99e-02	5.88e-01	1.70e-01	8.78e-01	1.86e-01	2.68e-01	4.09e-01	3.69e-01
TOC g/L	1.12e-01	1.05e+00	4.91e-01	5.10e-01	3.87e-01	4.70e-01	4.27e-01	3.84e-01
TIC g/L	5.14e-01	2.36e+00	8.42e-01	1.20e+00	8.83e-01	9.85e-01	9.85e-01	8.04e-01
SPG	1.00e+00	1.09e+00	1.03e+00	1.03e+00	1.02e+00	4.27e-02	1.03e+00	3.51e-02
TotSolids								
pH								
3H	5.24e+00	1.20e+01	5.68e+00	7.10e-01	6.28e+00	3.78e+00	4.49e+00	4.64e+00
14C	4.47e-03	7.47e-02		2.70e-02	1.96e-02	4.97e-02	2.20e-02	3.59e-02
54Mn								
59Mn								
60Co	1.06e+01	6.37e+00	5.64e+00	3.00e+00	8.02e+00	2.69e+00	6.40e+00	3.16e+00
63Ni								
79Se	1.12e-02	3.98e-02		4.80e-02	2.55e-02		3.27e-02	1.93e-02
90Sr	2.62e+00	2.95e+01	4.53e+01	4.20e+03	2.37e+01	2.16e+01	1.37e+03	2.09e+03
94Nb	9.31e+00	7.38e+00	5.51e+00	6.80e+00	7.49e+00	1.90e+00	7.27e+00	1.58e+00
95Nb	8.67e+00				8.67e+00		8.67e+00	
99Tc	1.08e+00	1.68e+01		1.50e+01	4.47e+00	1.11e+01	7.86e+00	8.60e+00
103Ru			2.10e+01		2.10e+01		2.10e+01	
106RuRh	2.66e+02	4.89e+02	3.98e+02	3.70e+02	3.49e+02	1.12e+02	3.56e+02	9.18e+01

Dilute Waste Analyses and Estimates								
Units: Molarity; uCi/L for radionuclides; others as noted								
	Analytical Results			Estimate	Analytical		Overall Dilute	
Component	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
113Sn	2.38e+01	5.02e+01	2.80e+01		2.89e+01	1.42e+01	2.89e+01	1.42e+01
129I	3.19e-02	4.24e-02		3.00e-02	3.41e-02	7.46e-03	3.28e-02	6.69e-03
134Cs	1.05e+01	3.97e+02	1.75e+02	1.50e+02	1.27e+02	1.94e+02	1.35e+02	1.60e+02
137Cs	6.54e+03	5.07e+04	1.52e+04	3.60e+04	1.57e+04	2.34e+04	2.22e+04	2.00e+04
144CePr	1.33e+02	2.72e+02	1.54e+02		1.59e+02	7.47e+01	1.59e+02	7.47e+01
154Eu	2.80e+01	1.61e+01	2.17e+01		4.07e+01	5.97e+00	4.07e+01	5.97e+00
155Eu	4.37e+01	6.89e+01	4.23e+01		4.63e+01	1.50e+01	4.63e+01	1.50e+01
226Ra	1.44e+02	7.76e+01	3.37e+02		2.15e+02	1.35e+02	2.15e+02	1.35e+02
234U	6.52e-03	9.25e-03			4.17e-03	1.93e-03	4.17e-03	1.93e-03
235U	3.39e-04	9.21e-04			2.72e-04	4.11e-04	2.72e-04	4.11e-04
238U	1.26e-03	3.02e-03			9.59e-04	1.24e-03	9.59e-04	1.24e-03
237Np				3.10e-04			3.10e-04	
238Pu				1.00e-01			1.00e-01	
239/240Pu	6.97e-03	9.89e-02	3.61e-01	1.10e-01	1.65e-01	1.84e-01	1.44e-01	1.52e-01
241Am	1.14e-02	2.15e-02	2.57e-01	1.20e-01	1.14e-01	1.39e-01	1.03e-01	1.14e-01
242Cm								
243Cm								
244Cm				6.60e-03			6.60e-03	
TB			1.56e+04		1.56e+04		1.56e+04	
AT			1.86e+00		1.86e+00		1.86e+00	
Volume L	4.16e+06	1.15e+06	3.75e+06	4.29e+06	9.06e+06			

Notes: Where no values are displayed for an analyte in a tank, the mean for that analyte across the tanks is calculated as the weighted (volume) mean of those reported.
 Less-than values calculated as real values.
 Not decayed: Decay date assumed to be October 1, 1993.

WHC-SD-WM-TI-528, Rev.

TABLE 1-2: DSSF Family Waste Summary

DSSF Family Wastes		Decayed to				10/01/93		[NOT Decayed]					
Units: Molarity: uCi/L for radionuclides; others as noted													
Waste	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Future	Required	Total	ConcWaste	
Component	106-AN	101-AW	105-AP	104-AN	105-AN	103-AN	DDSSF	Dilutes			Family	Std. Dev.	
Ag	3.37e-05	3.09e-04	2.00e-04			1.48e-04	7.10e-05	1.64e-05			8.90e-05	1.14e-04	
Al	3.44e-01	1.03e+00	1.60e-01	1.39e+00	1.74e+00	2.13e+00	1.50e-01	4.76e-02			4.92e-01	7.77e-01	
As	9.61e-07	1.33e-07	8.58e-08			2.14e-03	1.00e-04	8.85e-08			2.00e-04	1.07e-03	
B													
Ba	8.08e-05	6.80e-05	4.35e-05			1.17e-04	4.40e-05	6.13e-08			4.66e-05	3.04e-05	
Be						1.78e-03					1.78e-03		
Bi	6.94e-04	5.79e-04	3.70e-04			2.30e-04		5.91e-05			3.13e-04	2.08e-04	
Ca	2.25e-03	8.26e-04	1.08e-03			2.16e-03		2.73e-05			4.24e-04	7.30e-04	
Cd	4.41e-04	1.08e-05	6.92e-06			1.42e-04	4.05e-05	3.93e-08			6.45e-05	2.04e-04	
Co													
Cr	1.08e-02	3.09e-03	3.32e-03	1.30e-02	1.30e-02	1.63e-02	1.33e-03	2.19e-04			4.23e-03	5.49e-03	
Cu	6.90e-05	3.81e-04	2.42e-04			1.89e-04		3.89e-05			1.49e-04	1.33e-04	
Fe	1.24e-04	7.86e-04	2.00e-04	2.00e-04	2.00e-04	1.26e-03	3.15e-03	3.04e-04			1.78e-03	4.61e-04	
Hg	2.49e-07	7.82e-07	4.99e-07			7.98e-05	1.66e-07	4.11e-08			5.49e-08	3.96e-05	
K	2.76e-02	1.07e+00	8.57e-01	1.83e-01	1.57e-01	3.89e-01		1.11e-01			3.44e-01	4.21e-01	
La													
Li													
Mg	1.14e-04	2.16e-03	4.95e-04			1.18e-03	2.29e-03	2.73e-04			1.61e-03	8.96e-04	
Mn	1.01e-03	4.76e-04	3.05e-04			5.24e-04	1.77e-04	3.13e-05			2.62e-04	3.04e-04	
Mo	6.94e-04	6.00e-04	3.05e-04			9.17e-04		6.12e-05			4.24e-04	2.20e-04	
Na	3.93e+00	1.00e+01	6.35e+00	1.20e+01	1.20e+01	1.46e+01	4.82e+00	7.71e-01			6.00e+00	3.98e+00	
Nd													
Ni			2.15e-03			4.09e-04		1.75e-04			6.22e-04	1.23e-03	

A-6

WHC-SD-WM-TI-528, Rev. 0
TABLE 1-2 continued.

DSSF Family Wastes		Decayed to			10/01/93		[NOT Decayed]				
Units: Molarity; uCi/L for radionuclides, others as noted											
Waste	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Future	Required	Total	ConcWaste
Component	106-AN	101-AW	105-AP	104-AN	105-AN	103-AN		DDSSF	Dilutes	Family	Std. Dev.
P	1.97e-01		1.43e-02						2.26e-03	4.98e-02	1.29e-01
Pb	2.22e-03	1.46e-03	9.33e-04			3.47e-04		3.35e-04	7.75e-05	5.37e-04	7.96e-04
Pd											
Sb						1.31e-03				1.31e-03	
Se	1.70e-06	4.20e-07	2.73e-07			2.63e-03	6.74e-07		7.33e-08	1.75e-04	1.32e-03
Si		4.36e-03	3.53e-03			9.68e-03			4.40e-04	3.38e-03	3.34e-03
Sn											
Ta	7.18e-07										
Ti	7.33e-05	9.88e-05	6.38e-05			3.34e-04			1.88e-05	1.36e-05	
U g/L	1.68e-05	9.39e-04	6.06e-04			5.16e-04	9.08e-08		7.29e-03	1.37e-03	1.29e-04
V						3.14e-04				3.14e-04	
W						1.13e-03				1.13e-03	
Zn	1.44e-04	4.84e-03	1.16e-03			7.34e-04	2.00e-03		3.39e-04	1.66e-03	2.12e-03
Zr	3.05e-04	5.54e-04	3.59e-04			2.63e-04			5.65e-05	2.50e-04	1.28e-04
CN-	2.31e-04	1.03e-03	6.65e-04			1.29e-03	3.12e-04		6.19e-05	4.01e-04	4.61e-04
S-2											
NH4 +	7.22e-03	1.45e-02	2.34e-03								
NH3					6.99e-03	2.00e-02		5.20e-03	4.20e-03		6.12e-03
CO3-2	3.27e-01	2.05e-01	2.53e-01	4.72e-01	3.63e-01	1.49e-01				2.03e-02	9.20e-03
Cl-	6.94e-02	1.46e-01	7.28e-02	2.12e-01	2.40e-01	2.71e-01	1.05e-01		2.06e-02	2.12e-01	1.17e-01
F-	3.24e-03	4.02e-03	1.30e-01			3.87e-02	1.76e+00		1.41e-02	1.15e-01	8.60e-02
SO4-2	2.24e-02	1.07e-02	2.48e-02	6.82e-02	6.82e-02	1.67e-02	1.25e-01		1.56e-01	1.03e+00	5.96e-02
NO3-	1.09e+00	3.46e+00	2.66e+00	3.10e+00	3.12e+00	2.54e+00	1.51e+00		1.14e-02	7.63e-02	2.60e-02
									1.83e-01	1.72e+00	8.40e-01

WHC-SD-WM-TI-528, Rev.
TABLE 1-2 continued.

DSSF Family Wastes		Decayed to				10/01/93							
Units: Molarity: uCi/L for radionuclides; others as noted													
Waste	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Future	Required	Total	ConcWaste		
Component	106-AN	101-AW	105-AP	104-AN	105-AN	103-AN	DDSSF	Dilutes	Family	Std. Dev.			
NO2-	6.44e-01	2.19e+00	1.09e+00	1.92e+00	2.61e+00	2.99e+00	4.80e-01	7.83e-02	9.37e-01	8.96e-01			
PO4-3	1.94e-01	2.22e-02	1.62e-02	2.94e-02	2.00e-02	9.77e-03	1.85e-02	2.36e-03	2.69e-02	7.14e-02			
OH-	4.74e-01	5.07e+00	4.63e+00	4.09e+00	3.64e+00	5.74e+00	1.43e+00	4.09e-01	2.15e+00	1.85e+00			
TOC g/L	3.26e+00	2.46e+00	3.92e+00	5.53e+01	4.66e+01	6.13e-01	2.98e+00	4.27e-01	8.15e+00	2.51e+01			
TIC g/L		2.46e+00					6.79e+00	9.85e-01	5.191204				
SPG	1.23	1.58	1.347377	1.499809	1.503333	1.6	1.25e+00	1.03e+00	1.2805	1.40e-01			
TotSolids													
pH				13.5	13.5				13.5				
3H	2.68e+00	5.90e+00	7.40e+00			2.44e+00	5.49e+00	4.49e+00	5.07e+00	2.44e+00			
14C	3.35e-01	3.70e-01	2.36e-01			2.00e+00	1.51e-01	2.20e-02	2.85e-01	8.44e-01			
54Mn													
59Mn													
60Co	5.10e+00	1.94e+01	1.04e+01			1.20e+01	6.17e+01	6.40e+00	3.91e+01	5.92e+00			
63Ni													
79Se	2.40e-01	4.80e-01	3.06e-01			4.30e+01	1.86e-01	3.27e-02	3.03e+00	2.13e+01			
90Sr	2.01e+03	1.01e+03	1.90e+02	9.84e+03	3.23e+03	1.05e+04	1.82e+02	1.37e+03	1.82e+03	4.55e+03			
94Nb	2.30e+01	6.82e+01	4.35e+01			7.10e+00	5.76e+01	7.27e+00	4.33e+01	2.64e+01			
95Nb							6.67e+01	8.67e+00	5.34e+01				
99Tc	6.92e+01	1.52e+02	1.79e+01			1.70e+02	3.44e+01	7.86e+00	4.87e+01	7.14e+01			
103Ru							1.62e+02	2.10e+01	1.29e+02				
106RuRh	6.78e+01	4.18e+02	9.90e+01			1.73e-01	2.68e+03	3.56e+02	1.62e+03	1.86e+02			
113Sn							2.22e+02	2.89e+01	1.78e+02				
129I	7.50e-02	3.03e-01	4.18e-02			5.20e-01	2.63e-01	3.28e-02	2.18e-01	2.23e-01			

A-8

WHC-SD-WM-TI-528, Rev. 0
TABLE 1-2 continued.

DSSF Family Wastes			Decayed to				10/01/93							
Units: Molarity: uCi/L for radionuclides; others as noted														
Waste	Tank	Tank	Tank	Tank	Tank	Tank	Tank	[NOT Decayed]					Total	ConcWaste
Component	106-AN	101-AW	105-AP	104-AN	105-AN	103-AN	103-AN	Future	Required	Dilutes	Family	Std. Dev.		
134Cs	5.33e+00	5.20e+02	5.25e+02	7.20e+01	7.20e+01	5.75e+00	5.75e+00	9.80e+02	1.35e+02	1.35e+02	5.77e+02	2.52e+02		
137Cs	1.85e+05	4.83e+05	2.56e+05	7.56e+05	5.04e+05	6.13e+05	6.13e+05	1.21e+05	2.22e+04	2.22e+04	2.27e+05	2.15e+05		
144CePr								1.22e+03	1.59e+02	1.59e+02	9.80e+02			
154Eu								3.13e+02	4.07e+01	4.07e+01	2.51e+02			
155Eu								3.56e+02	4.63e+01	4.63e+01	2.85e+02			
226Ra								1.66e+03	2.15e+02	2.15e+02	1.32e+03			
234U						5.30e-02	5.30e-02	3.21e-02	4.17e-03	4.17e-03	3.37e-01			
235U						1.10e-03	1.10e-03	2.10e-03	2.72e-04	2.72e-04	1.97e-02			
238U						1.40e-02	1.40e-02	7.38e-03	8.59e-04	8.59e-04	7.94e-02			
237Np	2.11e+00	2.16e+00	1.39e+00			2.00e-02	2.00e-02		3.10e-04	3.10e-04	8.81e-01	9.98e-01		
238Pu	1.83e-02		3.67e-02			9.14e-01	9.14e-01		1.00e-01	1.00e-01	2.23e-01	5.12e-01		
239/240Pu	3.78e-02	1.14e+00	4.23e-02	1.04e+01	1.04e+01	1.90e+00	1.90e+00	1.27e+00	1.44e-01	1.44e-01	2.09e+00	5.03e+00		
241Am	6.02e-01	1.20e+00	1.33e+00	1.12e+04	1.12e+04	2.27e+00	2.27e+00	8.80e-01	1.03e-01	1.03e-01	1.35e+03	5.80e+03		
242Cm														
243Cm	4.23e-02	4.94e-02	3.07e-02								4.14e-02	9.42e-03		
244Cm						3.00e-01	3.00e-01		6.60e-03	6.60e-03	8.92e-02			
TB									1.56e+04	1.56e+04	1.56e+04			
AT									1.86e+00	1.86e+00	1.86e+00			
Volume L	3667985	3826969	3145609	3024479	4269852	3546854	30282640	9045989	60810376					

Notes:

Where no values are displayed for an analyte in a tank, the mean for that analyte across the tanks is calculated as the weighted (volume) mean of those reported.
 Less-than values calculated as real values. NH_4^+ and NH_3 jointly summarized as NH_3 in overall summary.
 Concentrate waste standard deviation is calculated using the first six tank data columns.

TABLE 1-3: DSSF Family Radiolytic Heat Loading¹

137Cs/137mBa Heat Equivalents - calc by parent concentration											
	Heat Equiv. (Ci 137Cs/137mBa/Ci)	106-AN	101-AW	105-AP	104-AN	105-AN	103-AN	DDSSF	Dilutes	Total	
60Co	3.1984	16.31067	62.17139	33.35944	0	0	38.24548	197.2573	20.48289	125.1419	
90Sr/Y	1.3967	2801.698	1403.93	265.7258	13739.06	4506.432	14726.28	254.4167	1908.786	2540.417	
106Ru/Rh	2.0004	135.5683	835.4356	197.9927	0	0	0.34575	5366.679	711.3283	3237.727	
134Cs	2.1113	11.25261	1097.556	1109.116	152.0717	152.0717	12.13998	2068.492	284.2719	1218.438	
137Cs/137mBa	1	115096.5	487772.2	255627.1	755513.2	504323.6	612820.1	120907.5	22239.97	227020	
144Ce/Pr	1.6624	0	0	0	0	0	0	2035.712	264.6428	1628.348	
Total		188061.3	486171.3	257233.3	769404.3	508982.1	627597.1	130830	25428.48	235770.1	
Heat Load Ratio											
%Volume (feed ratio)		100.0%	75.2%	100.0%	46.6%	71.6%	57.5%	100.0%			
Rqd Dilute for blending (L)		0	1263663	0	3471848	1691101	2619377	0			

Decay Date = 10/01/93.

¹ Radiolytic heat loading is a calculation of the heat released to the waste through high energy radiolytic decay. A "¹³⁷Cs/137mBa heat equivalent" is defined as the ratio of heat provided by one curie of the referenced decay chain relative to the heat released from the decay of one curie of ¹³⁷Cs and its high energy daughter ¹³⁷mBa. The basis for these calculations is provided in Hendrickson (1991a). These calculations result in evaluation of maximum feed fraction of each waste blended with dilute waste while complying with acceptance criteria for heat loading (Hendrickson, 1991b). A %Volume of 100% indicates that material may be fed without dilution.

WHC-SD-WM-TI-528, Rev. 1

TABLE 1-4: Pretreatment Waste Summary

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on 5M Na)		Mean
Ag							1.20e-03		4.08e-05
Al	4.38e-01	4.99e-01	3.00e-02	3.42e-02	4.20e-02	1.60e-02	5.50e-01	5.11e-01	4.05e-01
As							5.80e-03		1.97e-04
B					8.40e-03	9.70e-03	1.20e-02	1.69e-03	3.37e-03
Ba					2.80e-04	2.40e-04		9.75e-05	1.18e-04
Be									
Bi									
Ca					2.10e-03	3.00e-03	1.10e-01	4.77e-03	7.30e-03
Cd							4.70e-03		1.60e-04
Ce					2.10e-05	2.20e-05	4.10e-03		1.44e-04
Cr	1.05e-02	8.75e-03			7.60e-03	2.70e-03	2.70e-01	1.22e-02	1.92e-02
Cu							1.20e-02		4.08e-04
Fe	4.40e-05	1.51e-04			1.90e-03	5.80e-03	2.80e-01	1.28e-02	1.85e-02
Hg									
I	1.92e-01	1.44e-01	1.66e-01	1.26e-01	1.20e-01	8.00e-02	5.80e-02	2.04e-02	5.65e-02
La					4.70e-04	6.60e-04			1.15e-04
Li							2.00e-03		6.81e-05
Mn					1.10e-03	1.30e-03	4.90e-03	3.34e-03	4.05e-03
Mo					6.80e-05	3.00e-03	1.00e-01	5.27e-03	7.03e-03
N					3.20e-05	3.40e-04	5.60e-04	1.30e-03	8.54e-04
Ni	5.00e-01	5.00e-01	1.00e-01	1.00e-01	5.01e-03	5.02e-03	5.03e-03	5.00e-03	5.00e-03
Na					7.40e-04	3.40e-04	1.50e-03		1.20e-04
P					4.40e-04	6.30e-04	5.60e-03	7.40e-03	1.89e-03
Pb									
Pr							3.50e-03		1.19e-04
Rb									
S							1.60e-03		6.13e-05
Se							1.50e-03		6.13e-04
Si					3.70e-02	3.70e-02	2.90e-03		8.77e-03
Sr									
Ta									
Tb					1.90e-04	1.70e-04	1.80e-03		9.95e-05
Ti					1.40e-03	2.19e-03	1.74e-03	1.59e-03	4.24e-01
V									
W									
Zn					9.70e-05	3.80e-05	4.10e-03	3.97e-04	4.08e-04

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on 5M Na)		Mean
Zr	2.90e-05	1.28e-05			2.40e-01	2.40e-01	2.30e-03	4.97e-04	5.09e-02
CN-									
S-2									
NH4+									
NH3					1.40e-02	2.60e-02			3.99e-03
CO3-2							3.30e-01		1.12e-02
Cl-					6.60e-03	3.70e-03	1.10e-01	7.88e-02	5.51e-02
F-					1.69e+00	1.67e+00	2.20e-01	5.22e-02	3.95e-01
SO4-2	1.43e-01	2.19e-01			5.00e-04	3.70e-03	7.20e-02	6.81e-02	6.70e-02
NO3-	1.66e+00	1.80e+00	3.78e+00	4.09e+00	7.40e-01	7.70e-01	3.50e+00	5.13e+00	3.76e+00
NO2-	4.10e-01	4.48e-01	1.20e-02	1.31e-02	3.60e-02	2.20e-02	5.50e-01		7.42e-02
PO4-3	2.37e-02	3.21e-03					4.40e-01	2.83e-02	3.46e-02
OH-	1.29e+00		8.80e-01		2.60e-01	2.90e-01	6.50e-01		1.55e-01
TOC g/L	6.20e-02								3.54e-03
TIC g/L									
SPG					1.48	1.47	1.43		
TotSolids									
pH									
3H									
14C	1.70e+01	4.48e+01			5.90e-01	6.50e-01	1.50e+00		3.71e+00
54Mn									
59Mn									
60Co					5.00e+01	6.10e+01	1.20e+02		1.56e+01
63Ni							3.50e+03		1.19e+02
79Se									
90Sr	1.53e+03	2.91e+03			2.20e+03	2.40e+03	5.80e+04	3.32e+04	2.39e+04
94Nb									
95Nb					2.40e+04	6.00e+03			3.49e+03
99Tc	2.24e+02	5.92e+02			4.30e+00	4.70e+00	2.10e+02		5.47e+01
103Ru									
106RuRh	1.26e+03	5.35e+03			9.40e+03	5.60e+03	1.20e+03		2.07e+03
113Sn									
129I	6.38e-02	1.78e-01			1.10e-02	1.20e-02	2.90e-01		2.61e-02
134Cs					3.00e+02	2.60e+02	7.30e+01		6.21e+01
137Cs	4.75e+04	1.36e+05	1.71e+05	4.89e+05	1.50e+04	1.10e+04	1.50e+05	9.72e+03	3.67e+04
144CePr					1.20e+04	6.90e+03	1.20e+03		2.12e+03
154Eu					9.30e+00	6.80e+01	1.20e+03		4.79e+01

WHC-SD-WM-TI-528, Rev. 1
TABLE 1-4 continued.

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
NCRW (no additional PUREX Ops)									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on 5M Na)		Mean
155Eu					1.10e+01	8.00e+01	1.20e+03		4.91e+01
226Ra									
234U									
235U									
238U									
237Np							8.51e-03		2.90e-04
238Pu	2.71e-01	8.30e-01			9.15e-02	2.29e-01			9.41e-02
239/240Pu	1.87e+00	3.03e+00			1.18e+00	1.97e+00	4.90e+01	1.28e+00	3.08e+00
241Am	3.33e+01	3.14e+02			9.79e-02	8.48e-01	1.73e+02	3.00e+00	2.78e+01
242Cm									
243Cm									
244Cm							4.86e-01		1.65e-02
TB									
AT									
Volume L	3.49e+06	3.50e+06	1.12e+05	1.12e+05	7.57e+06	5.30e+06	2.08e+06	3.90e+07	6.12e+07
Additional analytes described for these wastes									
95Zr					1.20e+04	2.80e+03			1.73e+03
125Sb					2.50e+03	2.20e+03	1.20e+03		5.41e+02
152Eu							1.20e+02		4.08e+00
241Pu	1.69e+01	4.51e+01			1.47e+01	4.08e+01			8.90e+00
242Pu					2.28e-05	1.49e-04			1.57e-05

Note: Not Decayed. Decay date assumed as October 1, 1993.

WHC-SD-WM-TI-528, Rev. 0

TABLE 2-1: 241-AP-103 Validated Analysis Data

Tank 103AP Analyses				Sample	934	935	936	937	941	942	943	944	945	949
17-Dec-91	Component	Units	MW	<										Comp
	Ag	ppm	107.868	<	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	
	Al	ppm	26.98154		102	76	307	103	259	560	104	171	550	
	As	ppm	74.9216		0.052	0.035	0.055	0.0445	0.039	0.084	0.028	0.035	0.081	
	B	ppm	10.81											
	Ba	ppm	137.33	<	0.065	0.065	0.065	0.065	0.065	0.065	0.065	0.065	0.065	
	Be	ppm	9.01218											
	Bi	ppm	208.9804											
	Cs	ppm	40.08											
	Cd	ppm	112.41		0.0715	0.048	0.133	0.0645	0.124	0.183	0.081	0.097	0.18	
	Ce	ppm	140.12											
	Cr	ppm	51.996		3.535	2.05	4.87	3.38	4.48	6.8	0.353	0.415	6.4	
	Cu	ppm	63.546											
	Fe	ppm	55.847	<	0.435	0.481	0.89	0.435	1.355	2.67	0.63	0.435	0.435	
	Hg	ppm	200.59	<	0.0017	0.0017	0.0017	0.0017	0.002		0.005	0.002	0.002	
	K	ppm	39.0983											
	La	ppm	138.9055											
	Li	ppm	6.941											
	Mg	ppm	24.305	<	1.085	1.03	1.53	1.15	0.255	0.255	0.255	0.255	0.255	
	Mn	ppm	54.938	<	0.015	0.015	0.0515	0.015	0.062	0.034	0.015	0.015	0.023	
	Mo	ppm	95.94											
	Na	ppm	22.98977		3665	2320	2460	3820	6540	11700	3700	4870	12000	
	Nd	ppm	144.24											
	Ni	ppm	58.7											
	P	ppm	30.97376											

TABLE 2-1 continued.

Tank 103AP Analyses					Sample															
17-Dec-91				<	933	934	935	936	937	941	942	943	944	945	949					
Component	Units	MW													Comp					
Pb	ppm	207.2	<	0.4			0.4													
Pd	ppm	106.4																		
Sb	ppm	121.75																		
Se	ppm	78.96	<	0.02		0.005	0.005	0.005	0.005	0.02	0.007	0.005	0.005	0.008						
Si	ppm	28.0855																		
Sn	ppm	118.69																		
Ta	ppm	180.9479																		
Tl	ppm	47.9																		
U	g/L	238.029													0.00369					
V	ppm	50.9415																		
W	ppm	183.85																		
Zn	ppm	65.38	<	0.0335		0.02	1.21	0.55	0.221	0.048	0.309	0.02	0.02	0.309						
Zr	ppm	91.22																		
CN-	ppm	26.0177	<	1		0.495	0.584	0.469	0.527	0.605	0.61	0.511	0.552	0.61						
S-2	ppm	32.06																		
NH4 +	M	18.0383	<	0.0025		0.00125	0.0019	0.00125	0.00125	0.005	0.005	0.005	7e-04	0.004						
NH3	M	17.0304																		
CO3-2	M	60.0092																		
Cl-	ppm	35.453		36.55		34.5	49.8	31	17.8	51.1	92.9	38.3	39.8	103						
F-	ppm	18.9984		61.15		88.2	178	60.3	54.1	129.5	305	60.6	96.4	260						
SO4-2	ppm	96.0576		451.5		502	318	414	196	395.5	162	418	482	163						
NO3-	ppm	63.0049		1680		2060	3500	1720	3250	4480	9440	1620	2850	8780						
NO2-	ppm	46.0055		1135		983	1380	1130	1280	1255	1700	1120	1200	1810						
PO4-3	ppm	94.97136		127		147	151	121	135	137	149	112	134	168						

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-1 continued.

Tank 103AP Analyzes				Sample	934	935	936	937	941	942	943	944	945	949
17-Dec-91	Component	Unit	MW	933	934	935	936	937	941	942	943	944	945	949
	OH-	M	17.0073	0.0321	0.05	0.111	0.0658	0.0882	0.089	0.207	8e-04	0.058	0.197	Comp
	TOC	g/L	12.011	0.1095	0.15	0.13	0.12	0.15	0.091	0.091	0.088	0.1	0.091	
	TIC	g/L	12.011	0.544	0.498	0.522	0.43	0.46	0.449	0.65	0.53	0.544	0.512	
	SPG	g/mL		0.9975	1.008	1.02	1.002	1.017	0.995	1.004	0.992	0.994	1.006	
	TotSolids	wt%												
	pH													
	3H	uCi/L												5.24
	14C	uCi/L												0.00447
	54Mn	uCi/L												
	59Mn	uCi/L												
	60Co	uCi/L								10		12	11	9.48
	63Ni	uCi/L												
	79Se	uCi/L												0.01115
	90Sr	uCi/L												2.62
	94Nb	uCi/L								9.31				
	95Nb	uCi/L								9.3				8.045
	99Tc	uCi/L												1.08
	103Ru	uCi/L												
	106RuRh	uCi/L								340				192
	113Sn	uCi/L								30				17.6
	129I	uCi/L												0.03185
	134Cs	uCi/L		18.3	10.4	9.69	9.94	8.32	10.32	9.43	9.17	8.62	11.3	9.51
	137Cs	uCi/L		6700	7200	5800	7020	6590	6415	8500	6590	6930	4230	6010
	144CePr	uCi/L								170				95.65

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-1 continued.

Tank 103AP Analyses				Sample	934	935	936	937	941	942	943	944	945	949
17-Dec-91	Component	Unit	MW	933	934	935	936	937	941	942	943	944	945	949
	154Eu	uCi/L		<										Comp
	155Eu	uCi/L		<						22		32	32	25,95
	226Ra	uCi/L		<		48.3	50	50.2	26	22	47.4	32		25,35
	234U	uCi/L		<						43				244
	235U	uCi/L												0.00652
	238U	uCi/L												0.00034
	237Np	uCi/L												0.00126
	238Pu	uCi/L												
	239/240Pu	uCi/L		<										
	241Am	uCi/L		<										0.00697
	242Cm	uCi/L												0.01135
	243Cm	uCi/L												
	244Cm	uCi/L												
	TB	uCi/L												
	AT	uCi/L												

TABLE 2-2: 241-AW-106 Validated Analysis Data

[illegible]

TABLE 2-2 continued.

Tank 106AW Analytes		Sample	20-Sep-91																Comp
Component	Units		MW																
Pb	ppm		207.2	<R	11	48.6	48	40.8	322	326	327	328	329	330	348				
Pd	ppm		106.4																
Sb	ppm		121.75																
Se	ppm		78.96	<	0.01	0.01	0.001	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01				
Si	ppm		28.0855																
Sn	ppm		118.69																
Ta	ppm		180.9479																
Ti	ppm		47.9																
U	g/L		238.029																
V	ppm		50.9415																0.00947
W	ppm		183.85																
Zn	ppm		65.38	R	81.6	138	121	78	128	77.5	184	41.4	106	73.2					
Zr	ppm		91.22																
CN-	ppm		26.0177		3.405	2.49	2.43	2.49	2.57	0.836	0.761	2.4	0.37	2.1					
S-2	ppm		32.06																
NH4 +	M		18.0383	<	0.0033	0.00149	0.0015	0.00149	0.00139	0.002	0.018	0.001	0.002	0.001					
NH3	M		17.0304																
CO3-2	M		60.0092																
Cl-	ppm		35.453		557.5	431	447	470	489	432.5	1180	455	450	441					
F-	ppm		18.9984		8310	5900	6660	5840	5830										
SO4-2	ppm		96.0576		3885	2480	2560	2580	2490	2335	10600	2550	2350	2350					
NO3-	ppm		63.0049		33450	31600	36800	31400	32500	31100	75900	31900	30100	28800					
NO2-	ppm		46.0055		9050	8140	7350	7470	7450	8060	24000	8270	8060	7800					
PO4-3	ppm		94.97136		658.12	589	586	611	595	587.5	1820	605	584	653					

E.77

[illegible]

WHC-SD-WM-TI-528, Rev. 0

TABLE 2-3: 241-AW-I02 Validated Analysis Data

Tank 102AW Analyses												
Component	Units	MW		Sample	9394	9395	9396	9397	9401	9402	9403	9404
Ag	ppm	107.868	<									
Al	ppm	26.98154			1.15	0.82	0.8	0.8				
As	ppm	74.9216			476	482	491	501				
B	ppm	10.81							1.45	1.56	1.405	1.61
Ba	ppm	137.33	<		1.3	1.3	1.3	1.3				
Be	ppm	9.01218										
Bi	ppm	208.9804										
Ca	ppm	40.08										
Cd	ppm	112.41	<		0.4	0.4	0.4	0.4				
Ce	ppm	140.12										
Cr	ppm	51.996			10.75	10.4	10.9	10.6				
Cu	ppm	63.546										
Fe	ppm	55.847			45.65	50.6	23.9	6.17				
Hg	ppm	200.59	<						0.005	0.005	0.005	0.005
K	ppm	39.0983										
La	ppm	138.9055										
Li	ppm	6.941										
Mg	ppm	24.305			9.55	13.7	13.3	17.2				
Mn	ppm	54.938	<		0.3	0.3	3	0.3				
Mo	ppm	95.94										
Na	ppm	22.98977			16550	16600	17000	17000				
Nd	ppm	144.24										
Ni	ppm	58.7										
P	ppm	30.97376										

A-22

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-3 continued.

Tank 102AW Analytes		Sample	9394	9395	9396	9397	9401	9402	9403	9404
14-Jun-91	14-Jun-91									
Component	Units	MW	<							
Pb	ppm	207.2	<	8	8	8				
Pd	ppm	106.4								
Sb	ppm	121.75								
Se	ppm	78.96	<				0.005	0.005	0.005	0.005
Si	ppm	28.0855								
Sn	ppm	118.69								
Ta	ppm	180.9479								
Ti	ppm	47.9								
U	g/l	238.029								
V	ppm	50.9415								
W	ppm	183.85								
Zn	ppm	65.38		3.245	7.3	5.1	20.9			
Zr	ppm	91.22								
CN-	ppm	26.0177								
S-2	ppm	32.06								
NH4 +	M	18.0383	<							
NH3	M	17.0304								
CO3-2	M	60.0092								
Cl-	ppm	35.453								
F-	ppm	18.9984								
SO4-2	ppm	96.0576								
NO3-	ppm	63.0049								
NO2-	ppm	46.0055								
PO4-3	ppm	94.97136								

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-3 continued.

Tank 102AW Analyses		Unit	MW	<	Sample	9394	9395	9396	9397	9401	9402	9403	9404
14-Jun-91	Component												
	OH-	M	17.0073										
	TOC	g/L	12.011										
	TIC	g/L	12.011										
	SPG	g/mL											
	TotSolids	wt%											
	pH												
	3H	uCi/L											
	14C	uCi/L											
	54Mn	uCi/L											
	59Mn	uCi/L											
	60Co	uCi/L		<									
	63Ni	uCi/L											
	79Se	uCi/L											
	90Sr	uCi/L		R									
	84Nb	uCi/L		<									
	95Nb	uCi/L											
	99Tc	uCi/L											
	103Ru	uCi/L		<									
	106RuRh	uCi/L		<									
	113Sn	uCi/L		<									
	129I	uCi/L											
	134Cs	uCi/L		<									
	137Cs	uCi/L											
	144CePr	uCi/L		<									

[illegible]

A-27

E.86

TABLE 2-4: 241-AP-103 Analysis Summary

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	10	<	0.04	4.74e-10	3.71e-07	4.40e-15
Al	ppm	10		246.2	179.8245	9.12e-03	6.66e-03
As	ppm	10		0.04825	0.016199	6.44e-07	2.16e-07
B	ppm						
Ba	ppm	10	<	0.065	0	4.73e-07	0.00
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	10		0.11075	0.046661	9.85e-07	4.15e-07
Ce	ppm						
Cr	ppm	10		3.6943	2.207772	7.10e-05	4.25e-05
Cu	ppm						
Fe	ppm	10	<	0.8301	0.717151	1.49e-05	1.28e-05
Hg	ppm	9	<	0.002067	0.0011	1.03e-08	5.48e-09
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	10	<	0.721	0.508575	2.97e-05	2.09e-05
Mn	ppm	10	<	0.02604	0.017424	4.74e-07	3.17e-07
Mo	ppm						
Na	ppm	10		5312.5	3689.37	2.31e-01	1.60e-01
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	10	<	0.4	0	1.93e-06	0.00
Pd	ppm						
Sb	ppm						
Se	ppm	10	<	0.0083	0.006203	1.05e-07	7.86e-08
Si	ppm						

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	1		0.00369			
V	ppm						
W	ppm						
Zn	ppm	10	<	0.27405	0.374165	4.19e-06	5.72e-06
Zr	ppm						
CN-	ppm	10	<	0.5963	0.150586	2.29e-05	5.79e-06
S-2	ppm						
NH4+	M	10	<	2.75e-03	1.74e-03	2.75e-03	1.74e-03
NH3	M						
CO3-2	M						
Cl-	ppm	10		49.475	27.30044	1.40e-03	7.70e-04
F-	ppm	10		129.325	89.98548	6.81e-03	4.74e-03
SO4-2	ppm	10		350.2	131.9398	3.65e-03	1.37e-03
NO3-	ppm	10		4039	3081.787	6.41e-02	4.89e-02
NO2-	ppm	10		1299.3	264.141	2.82e-02	5.74e-03
PO4-3	ppm	10		138.1	16.27165	1.45e-03	1.71e-04
OH-	M	10		0.089866	0.066742	8.99e-02	6.67e-02
TOC	g/L	10		0.11203	0.024337		
TIC	g/L	10		0.51385	0.062412		
SPG	g/mL	10		1.00366	0.009484		
TotSolids	wt%						
pH							
3H	uCi/L	1		5.24			
14C	uCi/L	1		0.00447			
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	4	<	10.615	1.122304		

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-4 continued.

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L	1		0.01115			
90Sr	uCi/L	1		2.62			
94Nb	uCi/L	1		9.31			
95Nb	uCi/L	2	<	8.6725	0.887419		
99Tc	uCi/L	1		1.08			
103Ru	uCi/L						
106RuRh	uCi/L	2	<	266	104.6518		
113Sn	uCi/L	2	<	23.8	8.768124		
129I	uCi/L	1	<	0.03185			
134Cs	uCi/L	11	<	10.45455	2.732217		
137Cs	uCi/L	11		6544.091	1042.609		
144CePr	uCi/L	2	<	132.825	52.57339		
154Eu	uCi/L	4	<	27.9875	4.905843		
155Eu	uCi/L	10	<	43.695	18.37012		
226Ra	uCi/L	2	<	143.5	142.1285		
234U	uCi/L	1		0.00652			
235U	uCi/L	1		0.000339			
238U	uCi/L	1		0.001257			
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	1	<	0.00697			
241Am	uCi/L	1	<	0.01135			
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						

TABLE 2-5: 241-AW-106 Analysis Summary

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	10	<R	4.812	1.216487	4.46e-05	1.13e-05
Al	ppm	10	R	1675.7	1168.542	6.21e-02	4.33e-02
As	ppm	10		2.6235	0.541449	3.50e-05	7.23e-06
B	ppm						
Ba	ppm	10	<R	1.727	0.230846	1.26e-05	1.68e-06
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	10	<R	2.973	0.89098	2.64e-05	7.93e-06
Ce	ppm						
Cr	ppm	10	R	22.915	6.087604	4.41e-04	1.17e-04
Cu	ppm						
Fe	ppm	10	<R	74.56	50.42793	1.34e-03	9.03e-04
Hg	ppm	10	<R	0.01046	0.012889	5.21e-08	6.43e-08
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	10	<R	10.588	9.392319	4.36e-04	3.86e-04
Mn	ppm	10	R	6.7235	6.419986	1.22e-04	1.17e-04
Mo	ppm						
Na	ppm	10	R	39770	16568.78	1.73e+00	7.21e-01
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	10	<R	43.64	11.6957	2.11e-04	5.64e-05
Pd	ppm						
Sb	ppm						
Se	ppm	10	<	0.0082	0.003795	1.04e-07	4.81e-08
Si	ppm						

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	1		0.00947			
V	ppm						
W	ppm						
Zn	ppm	10	R	103.77	43.29342	1.59e-03	6.62e-04
Zr	ppm						
CN-	ppm	10		1.98515	0.982056	7.63e-05	3.77e-05
S-2	ppm						
NH4+	M	10	<	3.29e-03	5.10e-03	3.29e-03	5.10e-03
NH3	M						
CO3-2	M						
Cl-	ppm	10		535.3	229.5887	1.51e-02	6.48e-03
F-	ppm	5		6512	1066.804	3.43e-01	5.62e-02
SO4-2	ppm	10		3418	2564.419	3.56e-02	2.67e-02
NO3-	ppm	10		36454.99	13999.66	5.79e-01	2.22e-01
NO2-	ppm	10		9575	5092.607	2.08e-01	1.11e-01
PO4-3	ppm	10		728.862	384.3368	7.67e-03	4.05e-03
OH-	M	10		0.58838	0.261077	5.88e-01	2.61e-01
TOC	g/L	10		1.0466	0.475226		
TIC	g/L	10		2.3595	0.582773		
SPG	g/mL	10		1.08595	0.04359		
TotSolids	wt%						
pH							
3H	uCi/L	1		12			
14C	uCi/L	1		0.0747			
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	1	<	6.37			

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-5 continued.

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L	1		0.0398			
90Sr	uCi/L	1		29.45			
94Nb	uCi/L	1	<	7.38			
95Nb	uCi/L						
99Tc	uCi/L	1		16.8			
103Ru	uCi/L						
106RuRh	uCi/L	1	<	489			
113Sn	uCi/L	1	<	50.15			
129I	uCi/L	1	<R	0.0424			
134Cs	uCi/L	1	<	397			
137Cs	uCi/L	1		50650			
144CePr	uCi/L	1	<	271.5			
154Eu	uCi/L	1	<	16.05			
155Eu	uCi/L	1	<	68.85			
226Ra	uCi/L	1	<	77.55			
234U	uCi/L	1		0.009252			
235U	uCi/L	1		0.000921			
238U	uCi/L	1		0.003015			
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	1	<	0.09885			
241Am	uCi/L	1	<	0.02145			
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						

TABLE 2-6: 241-AW-102 Analysis Summary

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	4	<	0.8925	0.171925	8.27e-06	1.59e-06
Al	ppm	4		487.5	10.90871	1.81e-02	4.04e-04
As	ppm	4		1.50625	0.094989	2.01e-05	1.27e-06
B	ppm						
Ba	ppm	4	<	1.3	8.43e-09	9.47e-06	6.14e-14
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	4	<	0.4	4.21e-09	3.56e-06	3.75e-14
Ce	ppm						
Cr	ppm	4		10.6625	0.2136	2.05e-04	4.11e-06
Cu	ppm						
Fe	ppm	4		31.58	20.52946	5.65e-04	3.68e-04
Hg	ppm	4	<	0.005	1.45e-11	2.49e-08	7.22e-17
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	4		13.4375	3.128198	5.53e-04	1.29e-04
Mn	ppm	4	<	0.975	1.35	1.77e-05	2.46e-05
Mo	ppm						
Na	ppm	4		16787.5	246.2214	7.30e-01	1.07e-02
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	4	<	8	0	3.86e-05	0.00
Pd	ppm						
Sb	ppm						
Se	ppm	4	<	0.005	1.45e-11	6.33e-08	1.83e-16
Si	ppm						

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-6 continued.

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	4		3.67e-03	1.23e-03	1.54e-08	5.15e-09
V	ppm						
W	ppm						
Zn	ppm	4		9.13625	8.01573	1.40e-04	1.23e-04
Zr	ppm						
CN-	ppm	4		1.2825	0.081803	4.93e-05	3.14e-06
S-2	ppm						
NH4+	M	4	<	0.01033	0.008471	1.03e-02	8.47e-03
NH3	M						
CO3-2	M						
Cl-	ppm	4		465.25	202.4918	1.31e-02	5.71e-03
F-	ppm	4		4035	190.1754	2.12e-01	1.00e-02
SO4-2	ppm	4		2335	302.4897	2.43e-02	3.15e-03
NO3-	ppm	4		14337.5	213.6001	2.28e-01	3.39e-03
NO2-	ppm	4		2570	52.91503	5.59e-02	1.15e-03
PO4-3	ppm	4		174.5	5.446712	1.84e-03	5.74e-05
OH-	M	3		0.17	0.013892	1.70e-01	1.39e-02
TOC	g/L	4		0.491075	0.096256		
TIC	g/L	4		0.842	0.167531		
SPG	g/mL	4		1.025275	0.001578		
TotSolids	wt%						
pH							
3H	uCi/L	4		5.6825	0.137689		
14C	uCi/L						
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	4	<	5.635	2.382737		

WHC-SD-WM-TI-528, Rev. 0

TABLE 2-6 continued.

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L						
90Sr	uCi/L	4	R	45.3175	71.79467		
94Nb	uCi/L	4	<	5.5075	1.903827		
95Nb	uCi/L						
99Tc	uCi/L						
103Ru	uCi/L	4	<	21.025	7.30542		
106RuRh	uCi/L	4	<	397.875	88.20466		
113Sn	uCi/L	4	<	28	9.40709		
129I	uCi/L						
134Cs	uCi/L	4	<	174.875	11.06327		
137Cs	uCi/L	4		15237.5	593.5416		
144CePr	uCi/L	4	<	154.175	62.61301		
154Eu	uCi/L	4	<	21.7	11.53798		
155Eu	uCi/L	4	<	42.2625	20.86725		
226Ra	uCi/L	4	<	337.125	50.0506		
234U	uCi/L						
235U	uCi/L						
238U	uCi/L						
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	4		0.361225	0.619461		
241Am	uCi/L	4		0.25745	0.373926		
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L	4		15625	3118.092		
AT	uCi/L	4	<R	1.86	0.36		

TABLE 2-7: Future Dilute DSSF Waste Summary²

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
Ag	9.23e-06	7.10e-05
Al	1.95e-02	1.50e-01
As	1.30e-05	1.00e-04
B		
Ba	5.72e-06	4.40e-05
Be		
Bi		
Ca	0.00	0.00
Cd	5.27e-06	4.05e-05
Ce		
Cr	1.73e-04	1.33e-03
Cu		
Fe	4.10e-04	3.15e-03
Hg	2.16e-08	1.66e-07
K		
La		
Li		
Mg	2.97e-04	2.29e-03
Mn	2.30e-05	1.77e-04
Mo		
Na	6.27e-01	4.82e+00
Nd		
Ni		
P		

²

241-AP-106 concentration estimates developed in WHC-SD-WM-TP-117.

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-7 continued.

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
Pb	4.35e-05	3.35e-04
Pd		
Sb		
Se	8.77e-08	6.74e-07
Si		
Sn		
Ta		
Ti		
U g/L	1.18e-08	9.08e-08
V		
W		
Zn	2.60e-04	2.00e-03
Zr		
CN-	4.06e-05	3.12e-04
S-2		
NH4+	5.95e-03	5.20e-03
NH3		
CO3-2		
Cl-	1.36e-02	1.05e-01
F-	2.29e-01	1.76e+00
SO4-2	1.62e-02	1.25e-01
NO3-	1.97e-01	1.51e+00
NO2-	6.24e-02	4.80e-01
PO4-3	2.40e-03	1.85e-02
OH-	1.86e-01	1.43e+00
TOC g/L	3.87e-01	2.98e+00
TIC g/L	8.83e-01	6.79e+00

WHC-SD-WM-TI-528, Rev. 0
TABLE 2-7 continued.

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
SPG	1.02e+00	~1.25
TotSolids		
pH		
3H	6.28e+00	5.49e+00
14C	1.96e-02	1.51e-01
54Mn		
59Mn		
60Co	8.02e+00	6.17e+01
63Ni		
79Se	2.55e-02	1.96e-01
90Sr	2.37e+01	1.82e+02
94Nb	7.49e+00	5.76e+01
95Nb	8.67e+00	6.67e+01
99Tc	4.47e+00	3.44e+01
103Ru	2.10e+01	1.62e+02
106RuRh	3.49e+02	2.68e+03
113Sn	2.89e+01	2.22e+02
129I	3.41e-02	2.63e-01
134Cs	1.27e+02	9.80e+02
137Cs	1.57e+04	1.21e+05
144CePr	1.59e+02	1.22e+03
154Eu	4.07e+01	3.13e+02
155Eu	4.63e+01	3.56e+02
226Ra	2.15e+02	1.66e+03
234U	4.17e-03	3.21e-02
235U	2.72e-04	2.10e-03
238U	9.59e-04	7.38e-03

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
237Np		
238Pu		
239/240Pu	1.65e-01	1.27e+00
241Am	1.14e-01	8.80e-01
242Cm		
243Cm		
244Cm		
TB		
AT		
Volume L	9.06e+06	1177332
WVR		87.00%

Note: Evaporator product calculated as 87% WVR.

TABLE 3-1: Evaporator Campaign 84-3 Analysis Data³

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
Ag	ppm	107.868			
Al	M	26.8815		1.81	
As	ppm	74.9216			
B	ppm	10.81			
Ba	ppm	137.33			
Be	ppm	9.01218			
Bi	ppm	208.98			
Ca	ppm	40.08			
Cd	ppm	112.41			
Ce	ppm	140.12			
Cr	ppm	51.996		0.013	
Cu	ppm	63.546			
Fe	ppm	55.847		2e-04	
Hg	ppm	200.59			
K	ppm	39.0983			
La	ppm	138.906			
Li	ppm	6.941			
Mg	ppm	24.305			
Mn	ppm	54.938			
Mo	ppm	95.94			
Na	M	22.9898			
Nd	ppm	144.24			
Ni	ppm	58.7			
P	ppm	30.9738			
Pb	ppm	207.2			
Pd	ppm	106.4			
Sb	ppm	121.75			
Se	ppm	78.96			
Si	ppm	28.0855			
Sn	ppm	118.69			
Ta	ppm	180.948			
Tl	ppm	47.9			

³

Reference: SD-WM-PE-018

WHC-SD-WM-TI-528, Rev. 0
TABLE 3-1 continued.

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
U	g/L	238.029			
V	ppm	50.9415			
W	ppm	183.85			
Zn	ppm	65.38			
Zr	ppm	91.22			
CN-	ppm	26.0177			
S-2	ppm	32.06			
NH4+	M	18.0383			
NH3	M	17.0304			
CO3-2	M	60.0092		0.28	
Cl-	M	35.453			
F-	M	18.9984			
SO4-2	M	96.0576		0.016	
NO3-	M	63.0049		2.72	
NO2-	M	46.0055		1.87	
PO4-3	M	94.9714		0.007	
OH-	M	17.0073		4.00	
TOC	M	12.011		0.3189	
TIC	g/L	12.011			
SPG	g/mL			1.464	
TotSolids	wt %				
pH					
3H	uCi/L				
14C	uCi/L				
54Mn	uCi/L				
59Mn	uCi/L				
60Co	uCi/L				
63Ni	uCi/L				
79Se	uCi/L				
90Sr	uCi/L			1270	1019
94Nb	uCi/L				
95Nb	uCi/L				
99Tc	uCi/L				
103Ru	uCi/L				
106RuRh	uCi/L				

WHC-SD-WM-TI-528, Rev. 0
TABLE 3-1 continued.

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
113Sn	uCi/L				
129I	uCi/L				
134Cs	uCi/L				
137Cs	uCi/L			624000	504603
144CePr	uCi/L				
154Eu	uCi/L				
155Eu	uCi/L				
226Ra	uCi/L				
234U	uCi/L				
235U	uCi/L				
238U	uCi/L				
237Np	uCi/L				
238Pu	uCi/L				
239/240Pu	uCi/L			10.422	
241Am	uCi/L			11400	
242Cm	uCi/L				
243Cm	uCi/L				
244Cm	uCi/L				
TB	uCi/L				
AT	uCi/L				
Note: Pu (total) assumed to be 239					

WHC-SD-WM-TI-528, Rev. 0

TABLE 3-2: Evaporator Campaign 84-5 Analysis Data⁴

Evap Camp. 84-5 Analyses			Sample					
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	MW						
Ag	ppm	107.868						
Al	M	26.98154		1.3	1.39	1.21	1.25	1.11
As	ppm	74.9216						
B	ppm	10.81						
Ba	ppm	137.33						
Be	ppm	9.01218						
Bi	ppm	208.9804						
Ca	ppm	40.08						
Cd	ppm	112.41						
Ce	ppm	140.12						
Cr	ppm	51.996						
Cu	ppm	63.546						
Fe	ppm	55.847						
Hg	ppm	200.59						
K	ppm	39.0983		0.154	0.178	0.408	0.085	0.11
La	ppm	138.9055						
Li	ppm	6.941						
Mg	ppm	24.305						
Mn	ppm	54.938						
Mo	ppm	95.94						
Na	M	22.98977		14.35		11.48	11.53	10.64
Nd	ppm	144.24						
Ni	ppm	58.7						
P	ppm	30.97376						
Pb	ppm	207.2						
Pd	ppm	106.4						
Sb	ppm	121.75						
Se	ppm	78.96						
Si	ppm	28.0855						
Sn	ppm	118.69						
Ta	ppm	180.9479						
Ti	ppm	47.9						

4

Reference: SD-WM-PE-022

Evap Camp. 84-5 Analyses			Sample					
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	MW						
U	g/L	238.029						
V	ppm	50.9415						
W	ppm	183.85						
Zn	ppm	65.38						
Zr	ppm	91.22						
CN-	ppm	26.0177						
S-2	ppm	32.06						
NH4 +	M	18.0383						
NH3	M	17.0304	<	0.005				
CO3-2	M	60.0092		0.255	0.18	0.94	0.588	0.66
Cl-	M	35.453	<	0.215		0.2	0.23	0.187
F-	M	18.9984	<					
SO4-2	M	96.0576	<					0.078
NO3-	M	63.0049		2.88	2.31	4.09	3.14	3.4
NO2- ^c	M	46.0055		1.97	2.16	1.31	2.05	1.64
PO4-3	M	94.97136		0.02	0.022	0.055	0.026	0.052
OH-	M	17.0073		4.6	4.72	3.84	4.35	3.37
TOC	M	12.011		6.6	5.95	4.31	6.01	4.72
TIC	g/L	12.011						
SPG	g/mL			1.49	1.54	1.52	1.51	1.47
TotSolids	wt%							
pH								
3H	uCi/L							
14C	uCi/L							
54Mn	uCi/L							
59Mn	uCi/L							
60Co	uCi/L							
63Ni	uCi/L							
79Se	uCi/L							
90Sr	uCi/L			17100	9710	21600	18000	11000
94Nb	uCi/L							
95Nb	uCi/L							
99Tc	uCi/L							
103Ru	uCi/L							
106RuRh	uCi/L							

Evap Camp. 84-5 Analyses				Sample				
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	MW						
113Sn	uCi/L							
129I	uCi/L							
134Cs	uCi/L			1260				
137Cs	uCi/L			940000	1890000	783000	889000	665000
144CePr	uCi/L							
154Eu	uCi/L							
155Eu	uCi/L							
226Ra	uCi/L							
234U	uCi/L							
235U	uCi/L							
238U	uCi/L							
237Np	uCi/L							
238Pu	uCi/L							
239/240Pu	uCi/L							
241Am	uCi/L							
242Cm	uCi/L							
243Cm	uCi/L							
244Cm	uCi/L							
TB	uCi/L							
AT	uCi/L							

WHC-SD-WM-TI-528, Rev. 0

TABLE 3-3: Evaporator Campaign 85-3 Analysis Data⁵

Evap Camp. 85-3 Analysis				Sample				
03-Apr-85			<	R4680	R4681	R4683	R4684	R4687
Component	Units	MW						
Ag	ppm	107.868						
Al	M	26.98154		1.7		1.8		1.73
As	ppm	74.9216						
B	ppm	10.81						
Ba	ppm	137.33						
Be	ppm	9.01218						
Bi	ppm	208.9804						
Ca	ppm	40.08						
Cd	ppm	112.41						
Ce	ppm	140.12						
Cr	ppm	51.996						
Cu	ppm	63.546						
Fe	ppm	55.847						
Hg	ppm	200.59						
K	ppm	39.0983		0.14		0.18		0.15
La	ppm	138.9055						
Li	ppm	6.941						
Mg	ppm	24.305						
Mn	ppm	54.938						
Mo	ppm	95.94						
Na	M	22.98977		11.45		11.38		13.08
Nd	ppm	144.24						
Ni	ppm	58.7						
P	ppm	30.97376						
Pb	ppm	207.2						
Pd	ppm	106.4						
Sb	ppm	121.75						
Se	ppm	78.96						
Si	ppm	28.0855						
Sn	ppm	118.69						
Ta	ppm	180.9479						
Ti	ppm	47.9						

⁵

Reference: SD-WM-PE-023

Evap Camp. 85-3 Analyses				Sample				
03-Apr-85			<	R4680	R4681	R4683	R4684	R4687
Component	Units	MW						
U	g/L	238.029						
V	ppm	50.9416						
W	ppm	183.85						
Zn	ppm	65.38						
Zr	ppm	91.22						
CN-	ppm	26.0177						
S-2	ppm	32.06						
NH4 +	M	18.0383						
NH3	M	17.0304	<			0.02		0.02
CO3-2	M	60.0092		0.7		0.14		0.25
Cl-	M	35.453		0.28		0.24		0.2
F-	M	18.9984	<					
SO4-2	M	96.0576	<					
NO3-	M	63.0049		4.18		2.13		3.05
NO2-	M	46.0055		2.42		2.28		3.13
PO4-3	M	94.97136		0.03		0.01		0.02
OH-	M	17.0073		3.05		4.48		3.38
TOC	M	12.011		4.1		5.3		2.73
TIC	g/L	12.011						
SPG	g/mL			1.53		1.5		1.48
TotSolids	wt%							
pH				13.5				
3H	uCi/L							
14C	uCi/L							
54Mn	uCi/L							
59Mn	uCi/L							
60Co	uCi/L							
63Ni	uCi/L							
79Se	uCi/L							
90Sr	uCi/L			3950				
94Nb	uCi/L							
95Nb	uCi/L							
99Tc	uCi/L							
103Ru	uCi/L							
106RuRh	uCi/L							

WHC-SD-WM-TI-528, Rev. 0
TABLE 3-3 continued.

Evap Camp. 85-3 Analyses				Sample				
03-Apr-85			<	R4680	R4681	R4683	R4684	R4687
Component	Units	MW						
113Sn	uCi/L							
129I	uCi/L							
134Cs	uCi/L							
137Cs	uCi/L			613000				
144CePr	uCi/L							
154Eu	uCi/L							
155Eu	uCi/L							
226Ra	uCi/L							
234U	uCi/L							
235U	uCi/L							
238U	uCi/L							
237Np	uCi/L							
238Pu	uCi/L							
239/240Pu	uCi/L							
241Am	uCi/L							
242Cm	uCi/L							
243Cm	uCi/L							
244Cm	uCi/L							
TB	uCi/L							
AT	uCi/L							

WHC-SD-WM-TI-528, Rev. 0

TABLE 3-4: Evaporator Campaign 84-5 Analysis Summary

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
Ag	ppm	0				
Al	M	5		1.252	0.104019	
As	ppm	0				
B	ppm	0				
Ba	ppm	0				
Be	ppm	0				
Bi	ppm	0				
Ca	ppm	0				
Cd	ppm	0				
Ce	ppm	0				
Cr	ppm	0				
Cu	ppm	0				
Fe	ppm	0				
Hg	ppm	0				
K	ppm	5		0.187	0.128787	
La	ppm	0				
Li	ppm	0				
Mg	ppm	0				
Mn	ppm	0				
Mo	ppm	0				
Na	ppm	4		12	1.618991	
Nd	ppm	0				
Ni	ppm	0				
P	ppm	0				
Pb	ppm	0				
Pd	ppm	0				
Sb	ppm	0				
Se	ppm	0				
Si	ppm	0				
Sn	ppm	0				
Ta	ppm	0				
Ti	ppm	0				
U	g/L	0				
V	ppm	0				

WHC-SD-WM-TI-528, Rev. 0
TABLE 3-4 continued.

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
W	ppm	0				
Zn	ppm	0				
Zr	ppm	0				
CN-	ppm	0				
S-2	ppm	0				
NH4 +	M	0				
NH3	M	1		0.005		
CO3-2	M	5		0.5246	0.310783	
Cl-	ppm	4		0.208	0.018601	
F-	ppm	0				
SO4-2	ppm	1		0.078		
NO3-	ppm	5		3.164	0.656453	
NO2-	ppm	5		1.826	0.347606	
PO4-3	ppm	5		0.035	0.017059	
OH-	M	5		4.176	0.563143	
TOC	g/L	5		5.518	0.961182	
TIC	g/L	0				
SPG	g/mL	5		1.506	0.027019	
TotSolids	wt%	0				
pH		0				
3H	uCi/L	0				
14C	uCi/L	0				
54Mn	uCi/L	0				
59Mn	uCi/L	0				
60Co	uCi/L	0				
63Ni	uCi/L	0				
79Se	uCi/L	0				
90Sr	uCi/L	5		15482	4894.809	12506 79
94Nb	uCi/L	0				
95Nb	uCi/L	0				
99Tc	uCi/L	0				
103Ru	uCi/L	0				
106RuRh	uCi/L	0				
113Sn	uCi/L	0				
129I	uCi/L	0				

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
134Cs	uCi/L	1		1260		62.27367
137Cs	uCi/L	5		1033400	480346.1	841151.3
144CePr	uCi/L	0				
154Eu	uCi/L	0				
155Eu	uCi/L	0				
226Ra	uCi/L	0				
234U	uCi/L	0				
235U	uCi/L	0				
238U	uCi/L	0				
237Np	uCi/L	0				
238Pu	uCi/L	0				
239/240Pu	uCi/L	0				
241Am	uCi/L	0				
242Cm	uCi/L	0				
243Cm	uCi/L	0				
244Cm	uCi/L	0				
TB	uCi/L	0				
AT	uCi/L	0				

TABLE 3-5: Evaporator Campaign 85-3 Analysis Summary

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
Ag	ppm	0				
Al	M	3		1.743333	0.051316	
As	ppm	0				
B	ppm	0				
Ba	ppm	0				
Be	ppm	0				
Bi	ppm	0				
Cs	ppm	0				
Cd	ppm	0				
Ce	ppm	0				
Cr	ppm	0				
Cu	ppm	0				
Fe	ppm	0				
Hg	ppm	0				
K	ppm	3		0.156667	0.020817	
La	ppm	0				
Li	ppm	0				
Mg	ppm	0				
Mn	ppm	0				
Mo	ppm	0				
Na	M	3		11.97	0.961925	
Nd	ppm	0				
Ni	ppm	0				
P	ppm	0				
Pb	ppm	0				
Pd	ppm	0				
Sb	ppm	0				
Se	ppm	0				
Si	ppm	0				
Sn	ppm	0				
Ta	ppm	0				
Ti	ppm	0				
U	g/L	0				
V	ppm	0				

WHC-SD-WM-TI-528, Rev. 0
TABLE 3-5 continued.

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
W	ppm	0				
Zn	ppm	0				
Zr	ppm	0				
CN-	ppm	0				
S-2	ppm	0				
NH4+	M	0				
NH3	M	2		0.02	7.09e-11	
CO3-2	M	3		0.363333	0.296704	
Cl-	M	3		0.24	0.04	
F-	M	0				
SO4-2	M	0				
NO3-	M	3		3.12	1.026791	
NO2-	M	3		2.61	0.455741	
PO4-3	M	3		0.02	0.01	
OH-	M	3		3.636667	0.748755	
TOC	M	3		3.876667	1.547137	
TIC	g/L	0				
SPG	g/mL	3		1.503333	0.025166	
TotSolids	wt%	0				
pH		1		13.5		
3H	uCi/L	0				
14C	uCi/L	0				
54Mn	uCi/L	0				
59Mn	uCi/L	0				
60Co	uCi/L	0				
63Ni	uCi/L	0				
79Se	uCi/L	0				
90Sr	uCi/L	1		3950		3226.485
94Nb	uCi/L	0				
95Nb	uCi/L	0				
99Tc	uCi/L	0				
103Ru	uCi/L	0				
106RuRh	uCi/L	0				
113Sn	uCi/L	0				
129I	uCi/L	0				

TABLE 3-5 continued.

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
134Cs	uCi/L	0				
137Cs	uCi/L	1		613000		504323.6
144CePr	uCi/L	0				
154Eu	uCi/L	0				
155Eu	uCi/L	0				
226Ra	uCi/L	0				
234U	uCi/L	0				
235U	uCi/L	0				
238U	uCi/L	0				
237Np	uCi/L	0				
238Pu	uCi/L	0				
239/240Pu	uCi/L	0				
241Am	uCi/L	0				
242Cm	uCi/L	0				
243Cm	uCi/L	0				
244Cm	uCi/L	0				
TB	uCi/L	0				
AT	uCi/L	0				

WHC-SD-WM-TI-528, Rev. 0

TABLE 4-1: Concentrated Waste Summary Data - 101AW, 103AN⁶

Units: Molarity; uCi/L for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AN Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
Ag	M	3.09e-04	3.09e-04	mg/g	1.00e-02	1.48e-04
Al	M	1.03e+00	1.03e+00	mg/g	3.60e+01	2.13e+00
As	M	1.33e-07	1.33e-07	mg/g	1.00e-01	2.14e-03
B	M			mg/g		
Ba	M	6.80e-05	6.80e-05	mg/g	1.00e-02	1.17e-04
Be	M			mg/g	1.00e-02	1.78e-03
Bi	M	5.79e-04	5.79e-04	mg/g	3.00e-02	2.30e-04
Ca	M	8.26e-04	8.26e-04	mg/g	5.40e-02	2.16e-03
Cd	M	1.08e-05	1.08e-05	mg/g	1.00e-02	1.42e-04
Ce	M			mg/g		
Cr	M	3.09e-03	3.09e-03	mg/g	5.30e-01	1.63e-02
Cu	M	3.81e-04	3.81e-04	mg/g	7.50e-03	1.89e-04
Fe	M	7.86e-04	7.86e-04	mg/g	4.40e-02	1.26e-03
Hg	mg/L	1.57e-01	7.82e-07	mg/g	1.00e-02	7.98e-05
K	M	1.07e+00	1.07e+00	mg/g	9.50e+00	3.89e-01
La	M			mg/g		
Li	M			mg/g		
Mg	M	2.16e-03	2.16e-03	mg/g	1.80e-02	1.18e-03
Mn	M	4.76e-04	4.76e-04	mg/g	1.80e-02	5.24e-04
Mo	M	6.00e-04	6.00e-04	mg/g	5.50e-02	9.17e-04
Na	M	1.00e+01	1.00e+01	mg/g	2.10e+02	1.46e+01
Nd	M			mg/g		
Ni	M			mg/g	1.50e-02	4.09e-04
P	M			mg/g		
Pb	M	1.46e-03	1.46e-03	mg/g	4.50e-02	3.47e-04
Pd	M			mg/g		
Sb	M			mg/g	1.00e-01	1.31e-03
Se	M	4.20e-07	4.20e-07	mg/g	1.30e-01	2.63e-03
Si	M	4.36e-03	4.36e-03	mg/g	1.70e-01	9.68e-03
Sn	M			mg/g		

6

References: WHC-SD-WM-TRP-055 and SD-WM-TI-355, Rev. 1. Less-thans calculated as real values.

WHC-SD-WM-TI-528, Rev. 0
TABLE 4-1 continued.

Units: Molarity; uCi/L for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AN Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
Ta	M			mg/g		
Ti	M	9.88e-05	9.88e-05	mg/g	1.00e-02	3.34e-04
U	M	9.39e-04	9.39e-04	mg/g	7.70e-02	5.18e-04
V	M			mg/g	1.00e-02	3.14e-04
W	M			mg/g	1.30e-01	1.13e-03
Zn	M	4.84e-03	4.84e-03	mg/g	3.00e-02	7.34e-04
Zr	M	5.54e-04	5.54e-04	mg/g	1.50e-02	2.63e-04
CN-	M	1.03e-03	1.03e-03	mg/g	2.10e-02	1.29e-03
S-2	M			mg/g		
NH4 +	M	1.45e-02	1.45e-02	mg/g		
NH3	M			mg/g		
CO3-2	M	2.05e-01	2.05e-01	mg/g	5.60e+00	1.49e-01
Cl-	M	1.46e-01	1.46e-01	mg/g	6.00e+00	2.71e-01
F-	M	4.02e-03	4.02e-03	mg/g	4.60e-01	3.87e-02
SO4-2	M	1.07e-02	1.07e-02	mg/g	1.00e+00	1.67e-02
NO3-	M	3.46e+00	3.46e+00	mg/g	1.00e+02	2.54e+00
NO2-	M	2.19e+00	2.19e+00	mg/g	8.60e+01	2.99e+00
PO4-3	M	2.22e-02	2.22e-02	mg/g	5.80e-01	9.77e-03
OH-	M	5.07e+00	5.07e+00	mg/g	6.10e+01	5.74e+00
TOC g/L	g/L	2.46e+00	2.46e+00	mg/g	4.60e+00	6.13e-01
TIC g/L	g/L	2.46e+00	2.46e+00	mg/g		
SPG	g/cm3	1.56e+00	1.56e+00	g/cm3	1.60e+00	1.60e+00
TotSolids	wt%					
pH						
3H	uCi/L	7.07e+00	7.07e+00	Ci/L	4.00e-06	4.00e+00
14C	uCi/L	3.70e-01	3.70e-01	Ci/L	2.00e-06	2.00e+00
54Mn	uCi/L			Ci/L		
59Mn	uCi/L			Ci/L		
60Co	uCi/L	2.96e+01	2.96e+01	Ci/L	3.80e-05	3.80e+01
63Ni	uCi/L			Ci/L		
79Se	uCi/L	4.80e-01	4.80e-01	Ci/L	4.30e-05	4.30e+01
89/90Sr	uCi/L	1.09e+03	1.09e+03	Ci/L	1.30e-02	1.30e+04
94Nb	uCi/L	6.82e+01	6.82e+01	Ci/L	7.10e-06	7.10e+00
95Nb	uCi/L			Ci/L		

Units: Molarity; uCi/L for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AN Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
99Tc	uCi/L	1.52e+02	1.52e+02	Ci/L	1.70e-04	1.70e+02
103Ru	uCi/L			Ci/L		
106RuRh	uCi/L	3.70e+03	3.70e+03	Ci/L	6.80e-05	6.80e+01
113Sn	uCi/L			Ci/L		
129I	uCi/L	3.03e-01	3.03e-01	Ci/L	5.20e-07	5.20e-01
134Cs	uCi/L	1.53e+03	1.53e+03	Ci/L	1.10e-04	1.10e+02
137Cs	uCi/L	5.20e+05	5.20e+05	Ci/L	7.50e-01	7.50e+05
144CePr	uCi/L			Ci/L		
154Eu	uCi/L			Ci/L		
155Eu	uCi/L			Ci/L		
226Ra	uCi/L			Ci/L		
234U	uCi/L			Ci/L	5.30e-08	5.30e-02
235U	uCi/L			Ci/L	1.10e-09	1.10e-03
238U	uCi/L			Ci/L	1.40e-08	1.40e-02
237Np	g/L	3.06e-03	2.16e+00	Ci/L	2.00e-08	2.00e-02
238Pu	uCi/L			Ci/L	9.80e-07	9.80e-01
239/240Pu	uCi/L	1.15e+00	1.15e+00	Ci/L	1.90e-06	1.90e+00
241Am	uCi/L	1.20e+00	1.20e+00	Ci/L	2.30e-06	2.30e+00
242Cm	uCi/L			Ci/L		
243/4Cm	uCi/L	5.33e-02	5.33e-02	Ci/L		
244Cm	uCi/L			Ci/L	4.20e-07	4.20e-01
TB	uCi/L			Ci/L		
AT	uCi/L			Ci/L		
Volume	L		3.83e+06			3.49e+06

TABLE 4-2: Concentrated Waste Summary Data - 105AP, 106AN⁷

	Less-thans calculated as real values						
	105-AP Estimate			Jan-89	106-AN Analysis		Apr-89
		Top	Bottom	Uniform			Uniform
	Units	MEAN	MEAN	Unit mean	Units	MEAN	Unit mean
Ag	M	8.30e-05	2.80e-04	2.00e-04	mg/L	3.63e+00	3.37e-05
Al	M	2.80e-01	7.10e-02	1.60e-01	mg/L	9.28e+03	3.44e-01
As	M	4.00e-08	1.20e-07	8.58e-08	mg/L	7.20e-02	9.61e-07
B	M				mg/L		
Ba	M	2.00e-05	6.10e-05	4.35e-05	mg/L	1.11e+01	8.08e-05
Be	M				mg/L		
Bi	M	1.70e-04	5.20e-04	3.70e-04	mg/L	1.45e+02	6.94e-04
Ca	M	2.50e-04	1.70e-03	1.08e-03	mg/L	9.02e+01	2.25e-03
Cd	M	3.20e-06	9.70e-06	6.92e-06	mg/L	4.96e+01	4.41e-04
Ce	M				mg/L		
Cr	M	9.30e-04	5.10e-03	3.32e-03	mg/L	5.64e+02	1.08e-02
Cu	M	1.10e-04	3.40e-04	2.42e-04	mg/L	3.75e+00	5.90e-05
Fe	M	2.40e-04	1.70e-04	2.00e-04	mg/L	6.90e+00	1.24e-04
Hg	M	2.30e-07	7.00e-07	4.99e-07	mg/L	5.00e-02	2.49e-07
K	M	7.20e-01	9.60e-01	8.57e-01	mg/L	1.08e+03	2.76e-02
La	M				mg/L		
Li	M				mg/L		
Mg	M	6.50e-04	3.80e-04	4.95e-04	mg/L	2.78e+00	1.14e-04
Mn	M	1.40e-04	4.30e-04	3.06e-04	mg/L	5.57e+01	1.01e-03
Mo	M	1.80e-04	5.40e-04	3.86e-04	mg/L	6.66e+01	6.94e-04
Na	M	2.80e+00	9.00e+00	6.35e+00	mg/L	9.03e+04	3.93e+00
Nd	M				mg/L		
Ni	M	1.00e-03	3.00e-03	2.15e-03	mg/L		
P	M	6.70e-03	2.00e-02	1.43e-02	mg/L	6.11e+03	1.97e-01
Pb	M	4.40e-04	1.30e-03	9.33e-04	mg/L	4.60e+02	2.22e-03
Pd	M				mg/L		
Sb	M				mg/L		
Se	M	1.30e-07	3.80e-07	2.73e-07	mg/L	1.34e-01	1.70e-06
Si	M	1.30e-03	5.20e-03	3.53e-03	mg/L		
Sn	M				mg/L		

7

References: WHC-SD-WM-TP-130, WHC-SD-WM-TP-065, and SD-WM-TI-355, Rev. 1.

WHC-SD-WM-TI-528, Rev. 0
TABLE 4-2 continued.

	Less-thans calculated as real values						
	105-AP Estimate			Jan-89	106-AN Analysis		Apr-89
		Top	Bottom	Uniform			Uniform
	Units	MEAN	MEAN	Unit mean	Units	MEAN	Unit mean
Ta	M				mg/L	1.30e-01	7.18e-07
Tl	M	3.00e-05	8.90e-05	6.38e-05	mg/L	3.51e+00	7.33e-05
U	M	2.80e-04	8.50e-04	6.06e-04	g/L	4.00e-03	1.68e-05
V	M				mg/L		
W	M				mg/L		
Zn	M	1.50e-03	9.00e-04	1.16e-03	mg/L	9.44e+00	1.44e-04
Zr	M	1.70e-04	5.00e-04	3.59e-04	mg/L	2.78e+01	3.05e-04
CN-	M	3.10e-04	9.30e-04	6.65e-04	g/L	6.00e-03	2.31e-04
S-2	M				mg/L		
NH4 +	M	5.30e-03	1.40e-04	2.34e-03	mg/L	1.30e+02	7.22e-03
NH3	M				mg/L		
CO3-2	M	2.70e-01	2.40e-01	2.53e-01	M	3.27e-01	3.27e-01
Cl-	M	3.90e-02	9.80e-02	7.28e-02	mg/L	2.46e+03	6.94e-02
F-	M	1.70e-01	1.00e-01	1.30e-01	mg/L	6.16e+01	3.24e-03
SO4-2	M	3.40e-02	1.80e-02	2.48e-02	mg/L	2.15e+03	2.24e-02
NO3-	M	1.80e+00	3.30e+00	2.66e+00	mg/L	6.85e+04	1.09e+00
NO2-	M	5.40e-01	1.50e+00	1.09e+00	M	6.44e-01	6.44e-01
PO4-3	M	2.50e-02	9.70e-03	1.62e-02	mg/L	1.84e+04	1.94e-01
OH-	M	3.20e+00	5.70e+00	4.63e+00	M	4.74e-01	4.74e-01
TOC g/L	g/L	2.20e+00	5.20e+00	3.92e+00	g/L	3.26e+00	3.26e+00
TiC g/L	g/L				g/L		
SPG	g/cm3	1.25e+00	1.42e+00	1.35e+00	g/cm3	1.23e+00	1.23e+00
TotSolids	wt%				wt%		
pH							
3H	uCi/L	1.10e+01	8.60e+00	9.63e+00	uCi/L	3.44e+00	3.44e+00
14C	uCi/L	1.10e-01	3.30e-01	2.36e-01	uCi/L	3.35e-01	3.35e-01
54Mn	uCi/L				uCi/L		
59Mn	uCi/L				uCi/L		
60Co	uCi/L	8.90e+00	2.70e+01	1.93e+01	uCi/L	9.15e+00	9.15e+00
63Ni	uCi/L				uCi/L		
79Se	uCi/L	1.40e-01	4.30e-01	3.06e-01	uCi/L	2.40e-01	2.40e-01
89/90Sr	uCi/L	3.10e+02	1.40e+02	2.13e+02	uCi/L	2.23e+03	2.23e+03
94Nb	uCi/L	2.00e+01	6.10e+01	4.35e+01	uCi/L	2.30e+01	2.30e+01
95Nb	uCi/L				uCi/L		

WHC-SD-WM-TI-528, Rev. 0
TABLE 4-2 continued.

	Less-thans calculated as real values						
	105-AP Estimate			Jan-89	106-AN Analysis		Apr-89
		Top	Bottom	Uniform			Uniform
	Units	MEAN	MEAN	Unit mean	Units	MEAN	Unit mean
99Tc	uCi/L	8.30e+00	2.50e+01	1.79e+01	uCi/L	6.92e+01	6.92e+01
103Ru	uCi/L				uCi/L		
106RuRh	uCi/L	1.10e+03	3.30e+03	2.36e+03	uCi/L	1.39e+03	1.39e+03
113Sn	uCi/L				uCi/L		
129I	uCi/L	2.00e-02	5.80e-02	4.18e-02	uCi/L	7.50e-02	7.50e-02
134Cs	uCi/L	1.60e+03	3.20e+03	2.52e+03	uCi/L	2.37e+01	2.37e+01
137Cs	uCi/L	1.70e+05	3.70e+05	2.85e+05	uCi/L	2.05e+05	2.05e+05
144CePr	uCi/L				uCi/L		
154Eu	uCi/L				uCi/L		
155Eu	uCi/L				uCi/L		
226Ra	uCi/L				uCi/L		
234U	uCi/L				uCi/L		
235U	uCi/L				uCi/L		
238U	uCi/L				uCi/L		
237Np	uCi/L	7.05e-01	1.90e+00	1.39e+00	g/L	3.00e-03	2.12e+00
238Pu	uCi/L	1.80e-02	5.30e-02	3.80e-02	uCi/L	2.00e-02	2.00e-02
239/240 Pu	uCi/L	2.00e-02	5.90e-02	4.23e-02	uCi/L	3.78e-02	3.78e-02
241Am	uCi/L	1.00e+00	1.60e+00	1.34e+00	uCi/L	6.06e-01	6.06e-01
242Cm	uCi/L				uCi/L		
243/4Cm	uCi/L	1.60e-02	4.80e-02	3.43e-02	uCi/L	4.70e-02	4.70e-02
244Cm	uCi/L				uCi/L		
TB	uCi/L				uCi/L		
AT	uCi/L				uCi/L		
Volume	L	1.34e+06	1.80e+06	3.15e+06			3.67e+06

TABLE 4-3: Concentrated Waste Summary Data - 104AN, 105AN

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
Ag	ppm	107.868					
Al	M	26.98154	1.74e+00	1.25e+00	1.81e+00	1.39e+00	1.74e+00
As	ppm	74.9216					
B	ppm	10.81					
Ba	ppm	137.33					
Be	ppm	9.01218					
Bi	ppm	208.9804					
Cs	ppm	40.08					
Cd	ppm	112.41					
Ce	ppm	140.12					
Cr	ppm	51.996			1.30e-02	1.30e-02	1.30e-02
Cu	ppm	63.546					
Fe	ppm	55.847			2.00e-04	2.00e-04	2.00e-04
Hg	ppm	200.59					
K	ppm	39.0983	1.57e-01	1.87e-01		1.83e-01	1.57e-01
La	ppm	138.9055					
Li	ppm	6.941					
Mg	ppm	24.305					
Mn	ppm	54.938					
Mo	ppm	95.94					
Na	M	22.98977	1.20e+01	1.20e+01		1.20e+01	1.20e+01
Nd	ppm	144.24					
Ni	ppm	58.7					
P	ppm	30.97376					
Pb	ppm	207.2					
Pd	ppm	106.4					
Sb	ppm	121.75					
Se	ppm	78.96					
Si	ppm	28.0855					
Sn	ppm	118.69					
Ta	ppm	180.9479					
Ti	ppm	47.9					
U	g/L	238.029					
V	ppm	50.9415					

WHC-SD-WM-TI-528, Rev. 0
Table 4-3 continued.

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
W	ppm	183.85					
Zn	ppm	65.38					
Zr	ppm	81.22					
CN-	ppm	26.0177					
S-2	ppm	32.06					
NH4 +	M	18.0383					
NH3	M	17.0304	2.00e-02	5.00e-03		6.99e-03	2.00e-02
CO3-2	M	60.0092	3.63e-01	5.25e-01	2.80e-01	4.72e-01	3.63e-01
Cl-	M	35.453	2.40e-01	2.08e-01		2.12e-01	2.40e-01
F-	M	18.9984					
SO4-2	M	96.0576		7.80e-02	1.60e-02	6.82e-02	6.82e-02
NO3-	M	63.0049	3.12e+00	3.16e+00	2.72e+00	3.10e+00	3.12e+00
NO2-	M	46.0055	2.61e+00	1.83e+00	1.87e+00	1.92e+00	2.61e+00
PO4-3	M	94.97136	2.00e-02	3.50e-02	7.00e-03	2.94e-02	2.00e-02
OH-	M	17.0073	3.64e+00	4.18e+00	4.00e+00	4.09e+00	3.64e+00
TOC	g/L	12.011	4.66e+01	6.63e+01	3.83e+00	5.53e+01	4.66e+01
TIC	g/L	12.011					
SPG	g/mL		1.50e+00	1.51e+00	1.46e+00	1.50e+00	1.50e+00
TotSolids	wt%						
pH			1.35e+01			1.35e+01	1.35e+01
3H	uCi/L						
14C	uCi/L						
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L						
63Ni	uCi/L						
79Se	uCi/L						
90Sr	uCi/L		3.95e+03	1.55e+04	1.27e+03	1.20e+04	3.95e+03
94Nb	uCi/L						
95Nb	uCi/L						
99Tc	uCi/L						
103Ru	uCi/L						
106RuRh	uCi/L						
113Sn	uCi/L						
129I	uCi/L						

WHC-SD-WM-TI-528, Rev. 0
Table 4-3 continued.

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
134Cs	uCi/L			1.26e+03		1.25e+03	1.25e+03
137Cs	uCi/L		6.13e+05	1.03e+06	6.24e+05	9.18e+05	6.13e+05
144CePr	uCi/L						
154Eu	uCi/L						
155Eu	uCi/L						
226Ra	uCi/L						
234U	uCi/L						
235U	uCi/L						
238U	uCi/L						
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L				1.04e+01	1.04e+01	1.04e+01
241Am	uCi/L				1.14e+04	1.14e+04	1.14e+04
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						
Volume	L		4.58e+05	2.99e+06	5.62e+05	4.01e+06	3.68e+06

WHC-SD-WM-TI-528, Rev. 0

TABLE 5-1: Radioisotope Decay Data⁸

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
3	H	1.23e+01	y	3.89e+08	2.15e+16	9.66e+03	Beta	3He
14	C	5.73e+03	y	1.81e+11	9.89e+12	4.46e+00	Beta	14N
32	P	1.43e+01	d	1233792	6.34e+17	2.86e+05	Beta	32S
35	S	8.72e+01	d	7534080	9.50e+16	4.28e+04	Beta	35Cl
51	Cr	2.77e+01	d	2393626	2.05e+17	9.24e+04	EC	51V
54	Mn	3.12e+02	d	26974080	1.72e+16	7.74e+03	EC	54Cr
55	Fe	2.73e+00	y	86149889	5.29e+15	2.38e+03	EC	55Mn
59	Fe	4.45e+01	d	3845664	1.10e+17	4.97e+04	Beta	59Co
58	Co	7.09e+01	d	6124032	7.05e+16	3.18e+04	EC	58Fe
60	Co	5.27e+00	y	1.66e+08	2.51e+15	1.13e+03	Beta	60Ni
60	mCo	1.05e+01	m	628.2	6.64e+20	2.99e+08	IT,Beta	60Co (99.75%), 60Ni (0.25%)
59	Ni	7.60e+04	y	2.40e+12	1.77e+11	7.97e-02	EC	59Co
63	Ni	1.00e+02	y	3.16e+09	1.26e+14	5.67e+01	Beta	63Cu
65	Zn	2.44e+02	d	21064320	1.83e+16	8.24e+03	EC	65Cu
67	Ga	3.26e+00	d	281750.4	1.33e+18	5.98e+05	EC	67Zn
75	Se	1.20e+02	d	10348992	3.23e+16	1.45e+04	EC	75As
79	Se	6.50e+04	y	2.05e+12	1.55e+11	6.96e-02	Beta	79Br
85	Kr	1.07e+01	y	3.39e+08	8.70e+14	3.92e+02	Beta	85Rb
86	Rb	1.87e+01	d	1611360	1.81e+17	8.14e+04	Beta	86Sr
89	Sr	5.05e+01	d	4364928	6.45e+16	2.90e+04	Beta	89Y
90	Sr	2.91e+01	y	9.18e+08	3.03e+14	1.36e+02	Beta	90Y
90	Y	2.67e+00	d	230774.4	1.21e+18	5.43e+05	Beta	90Zr
91	Y	5.85e+01	d	5055264	5.44e+16	2.45e+04	Beta	91Zr
93	Zr	1.50e+06	y	4.73e+13	5.69e+09	2.56e-03	Beta	93Nb
95	Zr	6.40e+01	d	5531328	4.77e+16	2.16e+04	Beta	95Nb
93	mNb	1.61e+01	y	5.08e+08	5.30e+14	2.39e+02	IT	93Nb
94	Nb	2.00e+04	y	6.31e+11	4.22e+11	1.90e-01	Beta	94Mo
95	Nb	3.50e+01	d	3021408	8.72e+16	3.93e+04	Beta	95Mo
99	Tc	2.13e+05	y	6.72e+12	3.76e+10	1.70e-02	Beta	99Ru

8

Reference: Walker et al., 1989

A-67

WHC-SD-WM-TI-528, Rev. 0
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
99	mTc	6.01e+00	h	21621.6	1.17e+19	5.27e+06	IT	99Tc
103	Ru	3.93e+01	d	3392928	7.17e+16	3.23e+04	Beta	103Rh
106	Ru	1.02e+00	y	32187871	7.34e+15	3.31e+03	Beta	106Rh
103	mRh	5.61e+01	m	3367.2	7.22e+19	3.25e+07	IT	103Rh
106	Rh	2.18e+00	h	7848	3.01e+19	1.36e+07	Beta	106Pd
107	Pd	6.50e+06	y	2.05e+14	1.14e+09	5.14e-04	Beta	107Ag
110	Ag	2.46e+01	s	24.6	9.25e+21	4.17e+09	Beta,EC	110Cd (99.7%), 110Pd (0.3%)
110	mAg	2.50e+02	d	21582720	1.05e+16	4.75e+03	Beta,IT	110Cd (98.64%), 110Ag (1.36%)
113	mCd	1.41e+01	y	4.45e+08	4.98e+14	2.24e+02	Beta,IT	113In (99.9%), 113Cd (0.1%)
115	mCd	4.46e+01	d	3853440	5.65e+16	2.55e+04	Beta	115In
113	mIn	1.66e+00	h	5968.8	3.71e+19	1.67e+07	IT	113In
114	mIn	4.95e+01	d	4277664	5.14e+16	2.31e+04	IT,EC	114In (95.7%), 114Cd (4.3%)
113	Sn	1.15e+02	d	9944640	2.23e+16	1.00e+04	EC	113In
117	mSn	1.36e+01	d	1175904	1.82e+17	8.20e+04	IT	117Sn
119	mSn	2.93e+02	d	25315200	8.31e+15	3.74e+03	IT	119Sn
121	mSn	5.50e+01	y	1.74e+09	1.19e+14	5.37e+01	IT,Beta	121Sn (77.6%), 121Sb (22.4%)
123	Sn	1.29e+02	d	11162880	1.82e+16	8.22e+03	Beta	123Sb
125	Sn	9.63e+00	d	832032	2.41e+17	1.08e+05	Beta	125Sb
126	Sn	1.00e+05	y	3.16e+12	6.30e+10	2.84e-02	Beta	126Sb
124	Sb	6.02e+01	d	5201280	3.88e+16	1.75e+04	Beta	124Te
125	Sb	2.76e+00	y	87033478	2.30e+15	1.04e+03	Beta	125Te
126	Sb	1.24e+01	d	1071360	1.86e+17	8.36e+04	Beta	126Te
126	mSb	1.90e+01	m	1140	1.74e+20	7.85e+07	Beta,IT	126Te (86%), 126Se (14%)
123	mTe	1.20e+02	d	10342080	1.97e+16	8.87e+03	IT	123Te
125	mTe	5.80e+01	d	5011200	4.00e+16	1.80e+04	IT	125Te
127	Te	9.40e+00	h	33840	5.83e+18	2.62e+06	Beta	127I
127	mTe	1.09e+02	d	9417600	2.09e+16	9.43e+03	IT,Beta	127Te (97.6%), 127I (2.4%)
129	Te	1.16e+00	h	4176	4.65e+19	2.09e+07	Beta	129I
129	mTe	3.36e+01	d	2903040	6.69e+16	3.01e+04	IT,Beta	129Te (64%), 129I (36%)
125	I	6.01e+01	d	5196096	3.86e+16	1.74e+04	EC	125Te
129	I	1.57e+07	y	4.95e+14	3.92e+08	1.76e-04	Beta	129Xe
131	I	8.04e+00	d	694656	2.75e+17	1.24e+05	Beta	130Xe

WHC-SD-WM-TI-528, Rev. 0
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
133	Xe	5.24e+00	d	452995.2	4.16e+17	1.87e+05	Beta	133Cs
134	Cs	2.07e+00	y	65164660	2.87e+15	1.29e+03	Beta	134Ba
135	Cs	2.30e+06	y	7.26e+13	2.56e+09	1.15e-03	Beta	135Ba
137	Cs	3.02e+01	y	9.52e+08	1.92e+14	8.65e+01	Beta	137mBa, 137Ba
137	mBa	2.55e+00	m	153.12	1.19e+21	5.38e+08	IT	137Ba
141	Ce	3.25e+01	d	2808000	6.32e+16	2.85e+04	Beta	141Pr
144	Ce	2.85e+02	d	24589440	7.07e+15	3.19e+03	Beta	144Pr
143	Pr	1.36e+01	d	1172448	1.49e+17	6.73e+04	Beta	143Nd
144	Pr	1.73e+01	m	1036.8	1.68e+20	7.56e+07	Beta	144Nd
144	mPr	7.20e+00	m	432	4.03e+20	1.81e+08	IT,Beta	144Pr (99.96%), 144Nd (0.04%)
146	Pm	5.53e+00	y	1.75e+08	9.83e+14	4.43e+02	EC,Beta	146Nd (66.1%), 146Sm (33.9%)
147	Pm	2.62e+00	y	82785941	2.06e+15	9.27e+02	Beta	147Sm
148	Pm	5.37e+00	d	463968	3.65e+17	1.64e+05	Beta	148Sm
148	mPm	4.13e+01	d	3567456	4.74e+16	2.14e+04	Beta,IT	148Sm (95.4%), 148Pm (4.6%)
151	Sm	9.00e+01	y	2.84e+09	5.84e+13	2.63e+01	Beta	151Eu
152	Eu	1.35e+01	y	4.25e+08	3.87e+14	1.74e+02	EC,Beta	152Sm (72.08%), 152Gd (27.92%)
154	Eu	8.59e+00	y	2.71e+08	6.00e+14	2.70e+02	Beta	154Gd
155	Eu	4.71e+00	y	1.49e+08	1.09e+15	4.90e+02	Beta	155Gd
153	Gd	2.42e+02	d	20874240	7.84e+15	3.53e+03	EC	153Eu
160	Tb	7.23e+01	d	6246720	2.51e+16	1.13e+04	Beta	160Dy
192	Ir	7.38e+01	d	6378912	2.04e+16	9.21e+03	Beta,EC	192Pt (95.4%), 192Os (4.6%)
201	Tl	3.04e+00	d	262483.2	4.75e+17	2.14e+05	EC	201Hg
207	Tl	4.77e+00	m	286.2	4.23e+20	1.90e+08	Beta	207Pb
208	Tl	3.05e+00	m	183.18	6.57e+20	2.96e+08	Beta	208Pb
209	Pb	3.25e+00	h	11710.8	1.02e+19	4.61e+06	Beta	209Bi
211	Pb	3.61e+01	m	2166	5.48e+19	2.47e+07	Beta	211Bi
212	Pb	1.06e+01	h	38304	3.08e+18	1.39e+06	Beta	212Bi
211	Bi	2.14e+00	m	128.4	9.24e+20	4.16e+08	Alpha, Beta	207Tl (99.72%), 211Po (0.273%)
212	Bi	1.01e+00	h	3632.4	3.25e+19	1.46e+07	Alpha, Beta	208Tl (35.94%), 212Po (64.06%)
213	Bi	4.56e+01	m	2735.4	4.30e+19	1.94e+07	Alpha, Beta	209Tl (2.16%), 213Po (97.84%)
212	Po	2.98e-07	s	2.98e-07	3.96e+29	1.79e+17	Alpha	208Pb

WHC-SD-WM-TI-528, Rev. 0
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
213	Po	4.00e-06	s	0.000004	2.94e+28	1.32e+16	Alpha	209Pb
215	Po	1.78e-03	s	0.00178	6.54e+25	2.95e+13	Alpha	211Pb
216	Po	1.45e-01	s	0.145	8.00e+23	3.60e+11	Alpha	212Pb
217	At	3.20e-02	s	0.032	3.61e+24	1.62e+12	Alpha	213Bi
219	Rn	3.96e+00	s	3.96	2.89e+22	1.30e+10	Alpha	215Po
220	Rn	5.56e+01	s	55.6	2.05e+21	9.22e+08	Alpha	216Po
222	Rn	3.82e+00	d	330350.4	3.41e+17	1.54e+05	Alpha	218Po
221	Fr	4.80e+00	m	288	3.93e+20	1.77e+08	Alpha	217At
223	Fr	2.18e+01	m	1308	8.59e+19	3.87e+07	Beta	223Ra
223	Ra	1.14e+01	d	987984	1.14e+17	5.12e+04	Alpha	219Rn
224	Ra	3.66e+00	d	316224	3.54e+17	1.59e+05	Alpha	220Rn
225	Ra	1.49e+01	d	1287360	8.65e+16	3.89e+04	Beta	225Ac
226	Ra	1.60e+03	y	5.05e+10	2.19e+12	9.89e-01	Alpha	222Rn
228	Ra	5.76e+00	y	1.82e+08	6.04e+14	2.72e+02	Beta	228Ac
225	Ac	1.00e+01	d	864000	1.29e+17	5.80e+04	Alpha	221Fr
227	Ac	2.18e+01	y	6.87e+08	1.61e+14	7.23e+01	Beta, Alpha	227Th (98.62%), 223Fr (1.38%)
228	Ac	6.15e+00	h	22140	4.96e+18	2.23e+06	Beta	228Th
227	Th	1.87e+01	d	1617408	6.82e+16	3.07e+04	Alpha	223Ra
228	Th	1.91e+00	y	60368036	1.82e+15	8.20e+02	Alpha	224Ra
229	Th	7.30e+03	y	2.30e+11	4.75e+11	2.14e-01	Alpha	225Ra
230	Th	7.54e+04	y	2.38e+12	4.58e+10	2.06e-02	Alpha	226Ra
231	Th	1.06e+00	d	91843.2	1.18e+18	5.32e+05	Beta	231Pa
232	Th	1.40e+10	y	4.42e+17	2.44e+05	1.10e-07	Alpha	228Ra
234	Th	2.41e+01	d	2082240	5.14e+16	2.32e+04	Beta	234Pa
231	Pa	3.28e+04	y	1.03e+12	1.05e+11	4.72e-02	Alpha	227Ac
233	Pa	2.70e+01	d	2332800	4.61e+16	2.08e+04	Beta	233U
234	mPa	1.17e+00	m	70.2	1.52e+21	6.87e+08	Beta, IT	234U (99.87%), 234Pa (0.13%)
232	U	7.00e+01	y	2.21e+09	4.89e+13	2.20e+01	Alpha	228Th
233	U	1.59e+05	y	5.02e+12	2.14e+10	9.64e-03	Alpha	229Th
234	U	2.46e+05	y	7.76e+12	1.38e+10	6.21e-03	Alpha	230Th
235	U	7.04e+08	y	2.22e+16	4.80e+06	2.16e-06	Alpha	231Th
236	U	2.34e+07	y	7.39e+14	1.44e+08	6.47e-05	Alpha	232Th

WHC-SD-WM-TI-528, Rev. 0
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
238	U	4.47e+09	y	1.41e+17	7.46e+05	3.36e-07	Alpha	234Th
236	Np	1.55e+05	y	4.89e+12	2.17e+10	9.77e-03	EC,Beta,Alpha	236U,236Pu,232Pa (91/8.9/0.2%)
237	Np	2.14e+06	y	6.75e+13	1.56e+09	7.05e-04	Alpha	233Pa
239	Np	2.36e+00	d	203472	5.15e+17	2.32e+05	Beta	239Pu
236	Pu	2.87e+00	y	90567832	1.17e+15	5.28e+02	Alpha	232U
238	Pu	8.77e+01	y	2.77e+09	3.80e+13	1.71e+01	Alpha	234U
239	Pu	2.41e+04	y	7.61e+11	1.38e+11	6.20e-02	Alpha	235U
240	Pu	6.56e+03	y	2.07e+11	5.04e+11	2.27e-01	Alpha	236U
241	Pu	1.44e+01	y	4.54e+08	2.29e+14	1.03e+02	Beta	241Am
242	Pu	3.75e+05	y	1.18e+13	8.74e+09	3.94e-03	Alpha	238U
244	Pu	8.00e+07	y	2.52e+15	4.07e+07	1.83e-05	Alpha,SPF	240U(99.85%),fiss.prod(0.125%)
241	Am	4.33e+02	y	1.37e+10	7.61e+12	3.43e+00	Alpha	237Np
242	Am	1.60e+01	h	57672	1.79e+18	8.08e+05	Beta,EC	242Cm (82.7%), 242Pu (17.3%)
242	mAm	1.41e+02	y	4.45e+09	2.33e+13	1.05e+01	IT,Alpha	242Am (99.55%), 238Np (0.45%)
243	Am	7.37e+03	y	2.33e+11	4.43e+11	2.00e-01	Alpha	239Np
242	Cm	1.63e+02	d	14065920	7.36e+15	3.31e+03	Alpha	238Pu
243	Cm	2.91e+01	y	9.18e+08	1.12e+14	5.05e+01	Alpha,EC	239Pu (99.76%), 243Am (0.24%)
244	Cm	1.81e+01	y	5.71e+08	1.80e+14	8.09e+01	Alpha	240Pu
245	Cm	8.50e+03	y	2.68e+11	3.81e+11	1.72e-01	Alpha	241Pu
246	Cm	4.76e+03	y	1.50e+11	6.78e+11	3.05e-01	Alpha	242Pu
247	Cm	1.56e+07	y	4.92e+14	2.06e+08	9.28e-05	Alpha	243Pu
248	Cm	3.48e+05	y	1.10e+13	9.19e+09	4.14e-03	Alpha,SPF	244Pu(91.74%),fiss.prod(8.26%)
252	Cf	2.64e+00	y	83246670	1.19e+15	5.38e+02	Alpha,SPF	248Cm(96.908%),fiss.prod(3.092%)

Appendix F

Permanent Isolation Barrier and Warning Marker System

Appendix F

Permanent Isolation Barrier and Warning Marker System^(a)

C. T. Kincaid, Pacific Northwest Laboratory

F.1 Introduction

A multi-year program entitled the "Hanford Site Permanent Isolation Barrier Development Program (BDP)" has been organized to develop, test, and evaluate protective barrier and warning marker systems for use at Hanford. Initial work on barriers at the Hanford Site was begun in the early 1980s and focused primarily on constructability of surface covers (Phillips et al. 1985). Direction for the overall program was first formulated and published in a program plan by Adams and Wing (1986). That plan has been updated in Wing et al. (1992). Material for this appendix, which describes the isolation barrier and marker system, has been drawn from these program plan documents, a peer review report (Wing 1992), and the testing and monitoring plan for a prototype barrier (Gee et al. 1993).

The Operations and Engineering Contractor for the U.S. Department of Energy's (DOE) Hanford Site, Westinghouse Hanford Company (WHC), and DOE's Research and Development Contractor for the Hanford Site, Pacific Northwest Laboratory (PNL), are jointly developing and testing protective barrier and warning marker systems. Permanent isolation barrier and warning marker systems use engineered layers of natural materials to create an integrated structure with redundant protective features. The emphasis of this program has been on the development of barriers and markers for above-grade (mounded barrier) application to existing waste sites where the soil profile should not be disturbed. However, the barrier design described herein is also relevant and applicable to barriers at new waste disposal sites such as the Hanford Grouted Waste Facility. Drawings of conceptual permanent isolation barrier and warning marker systems are shown in Figures F.1 and F.2. The natural construction materials (e.g., fine soil, sand, gravel, rip-rap, clay, asphalt) have been selected to optimize barrier performance and longevity. The

-
- (a) In April 1993 a new prototype design for the permanent isolation barrier was issued. It differs from the design described in this appendix. Certainly, as data are gathered and the performance of the 1993 prototype is assessed, the design will be revised. Since one cannot assert that any design described here is final (i.e., because it will be constructed during site closure), it has been decided not to revise this text. The interested reader can obtain the new prototype design by acquiring the following report: WHC. 1993. *Prototype Surface Barrier at 200-BP-1 Operable Unit*, WHC-SD-EN-TI-142, Rev. 0, prepared by Kaiser Engineers Hanford for Westinghouse Hanford Company, Richland, Washington.

Figure F.1. Conceptual Permanent Isolation Surface Barrier and Warning Marker System for an Above Grade Application

S9211085.2

Figure F2. Isolation Barrier and Warning Marker System

objective of current designs is to use natural materials to develop a maintenance-free permanent isolation barrier and warning marker system that isolates wastes for a minimum of 1,000 years by limiting water drainage to near-zero amounts; reducing the likelihood of plant, animal, and human intrusion; controlling the exhalation of noxious gases; and minimizing erosion-related problems.

F.1.1 Short-Term versus Long-Term Barriers

Existing short-term barrier designs currently are available [U.S. Environmental Protection Agency (EPA) 1982, 1990]. In general, the design life of these covers is for relatively short periods, such as the 30-year post-closure period specified by the *Resource Conservation and Recovery Act (RCRA) of 1976*.

The performance of barriers during this relatively short period can be monitored, and maintenance activities can be performed to correct any problems that might be encountered. However, there exist waste management situations in which it is desirable to isolate wastes for much longer periods than the 30-year post-closure period (i.e., hundreds to a thousand years). For these waste management situations, the relatively short-term (RCRA) designs are not satisfactory. For example, many synthetic construction materials that might be effective for tens of years (e.g., geosynthetics) cannot be relied on to perform satisfactorily (or even exist) over 1,000 years. Consequently, a need arises for a long-term, permanent isolation barrier.

F.2 Performance Objectives

To direct the development of protective barrier and warning marker systems, performance objectives for the barriers and markers have been defined. The following list summarizes these performance objectives. The objectives are intended to be broad enough to encompass the various regulatory requirements for the types of wastes anticipated to be disposed of in shallow land deposits using barriers at the Hanford Site and other DOE sites in the arid and semiarid western United States.

- Functions in a semiarid to subhumid climate
- Limits the recharge of water through the waste to the water table to near-zero amounts; a long-term annual average of 0.05 cm (0.02 in.) of water per year [i.e., a drainage rate of approximately 2×10^{-9} cm/s]
- Remains maintenance free by minimizing the likelihood of plant, animal, or human intrusion, and minimizing the likelihood of wind and water erosion
- Lasts for a minimum of 1,000 years.

The BDP goal has been to provide defensible evidence that final barrier design(s) will control water infiltration; plant and animal intrusion; and wind and water erosion for a minimum of 1,000 years and will protect human health and the environment in accordance with applicable or relevant and appropriate requirements. In the event that institutional control is lost, warning marker systems will be provided to inform inadvertent human intruders (Adams and Kaplan 1986; Kaplan and Adams 1986).

The protective barrier is designed to prevent or minimize contaminant migration to the accessible environment through the following pathways (Figures F.3 and F.4):

S9211085.3

Figure F.3. Potential Problems of the Current Waste Management Situation

- Water infiltration--the infiltration and percolation of water through the waste zone leading to the leaching and subsequent transport of radionuclides and other contaminants to the water table.
- Biointrusion--the penetration of deep-rooting plants and burrowing animals into the waste zone below. The deep-rooting plants could draw radionuclides and other contaminants into its root system and subsequently translocate the contaminants to the above-ground portion of the plant. The contaminants in the above-grade portion of the plant could then be dispersed by wind or by animals that eat the plants. Animals burrowing directly into the waste zone could contact contaminants and subsequently bring them to the earth's surface as part of the soil castings. Erodible loose soil, cast to the surface by burrowing animals, could contribute

Figure F.4. Cross Section of a Conceptual Permanent Isolation Barrier and Warning Marker System

to accelerated erosion of the fine-soil surface layer. In addition, the presence of animal burrows may provide preferential pathways for infiltrating water to gain access to the waste zone.

- Wind and water erosion--the removal of the surface soils at a waste site from the effects of erosive forces. Erosion-related problems could provide a direct pathway for contaminant transport if the erosive forces are strong enough to remove the surface soils and expose the buried wastes to the accessible environment. A more probable scenario is for wind and water erosion to reduce the thickness of soils overlying a waste zone such that another transport pathway (i.e., water infiltration) becomes a more serious concern.
- Human interference--the inadvertent or intentional intrusion of humans into the waste sites (assuming institutional control is lost) and subsequent dispersion of contaminants.
- Gaseous release--the diffusion of noxious gases from the waste zone to the accessible environment.

F.3 Barrier Design

Engineered barrier and marker systems have been proposed to protect wastes disposed of in shallow land deposits from the transport pathways identified above. The protective barrier and warning marker systems consist of a variety of different materials (e.g., fine soil, sand, gravel, rip-rap, asphalt, clay, etc.) placed in layers to form an above-grade mound or at-grade profile directly over the waste zone. Surface markers are placed around the periphery of the waste sites to inform future generations of the nature and hazards of the buried wastes (see Figure F.1). In addition, throughout the protective barrier, subsurface markers are placed to warn any inadvertent human intruders of the dangers of the wastes below (Figure F.5).

The protective barrier design consists of a fine-soil layer overlying other layers of coarser materials including sand, gravel, or basalt rip-rap. Each of these layers shown in Table F.1 serves a distinct purpose. The fine-soil layer acts as a medium in which moisture is stored until the processes of evaporation and transpiration can recycle excess water back to the atmosphere. The fine-soil layer also provides the medium for establishing plants that are necessary for transpiration to take place. McGee Ranch silt loam

Figure F.5. Placement of Surface and Subsurface Markers

Table F.1. The Vertical Layering and Materials of the Protective Barrier

Layer Thickness	Description	Comment
2 m (6.6 ft)	McGee Ranch Silt Loam	The McGee Ranch silt loam will be placed in two lifts; 1.0 m (3.3 ft) of clean silt-loam soil will be placed immediately above the sand filter, then 1.0 m (3.3 ft) of silt mixed with pea gravel will be placed and shaped to the grade elevation of the site.
15 cm (5.9 in.)	Sand Filter	This sand will act as a hydraulic filter between the overlying silt and the underlying crushed rock gravel. A woven geotextile is to be installed between sand and silt layers.
30 cm (11.8 in.)	Gravel Filter	This crushed rock gravel filter will act as a hydraulic filter between the overlying fine sand filter and the underlying fractured basalt core of the barrier system.
50 cm (20 in.)	Basalt Rip-Rap	The fractured basalt rip-rap is the primary capillary break in the isolation barrier system. This media is to have a minimum of fines in its grain size distribution to ensure a considerable open porosity. The physics of unsaturated water flow require water to nearly reach saturation in the silts overlying the sand filter before water will enter the sand, and to nearly reach saturation in the sand overlying the gravel filter before water will enter the gravel.
30 cm (11.8 in.)	Gravel	This gravel layer acts as a cushion between the basalt rip-rap and the asphalt. It ensures against damage to the asphalt during placement of the basalt.
15 cm (5.9 in.)	Asphalt	Asphalt is placed in two lifts to provide added assurance that adequate compaction is achieved. In addition, this ensures that preferential flow does not occur through single joints or localized areas of lower integrity (e.g., lower compaction or higher conductivity) in a single layer.

is currently the fine-soil of choice because it will create a favorable environment for containing the biological cycles in the upper portion of the barrier, thereby reducing biointrusion into the lower layers. The coarser materials (i.e., successively coarser sand, gravel, and basalt rip-rap) that are placed directly below the fine-soil layer create a capillary break that inhibits the downward percolation of water through the barrier. The coarser materials will also help to deter inadvertent human intruders from digging deeper into the barrier profile. A low-permeability layer placed in the barrier profile below the capillary break is included in the protective barrier design. The purpose of the low-permeability layer is to divert any percolating water that gets through the capillary break away from the waste zone, and to limit the upward

movement of gases from the waste zone. The low-permeability material of choice is asphalt, which is hydrophobic (i.e., not wetted by water) and should be an excellent redundant barrier to recharge.

Because the barrier must perform for at least 1,000 years without maintenance, natural construction materials (e.g., fine soil, sand, gravel, cobble, crushed basalt rip-rap, asphalt, clay, etc.) have been selected to optimize barrier performance and longevity. Most of these natural materials are available in large quantities on the Hanford Site and are known to have existed in place for thousands of years or longer. In contrast to natural materials, the ability of man-made construction materials to survive and function properly for a thousand years is not known. Because of this uncertainty, man-made construction materials are not relied upon in this design.

The need for a maintenance-free barrier that lasts for a minimum of a thousand years necessitates the use of passive, as opposed to active, systems. Active systems are impractical because they require human involvement to operate, monitor, and maintain. For example, a leachate collection and removal system requires monitoring the collection of leachate and removing it from the collection system using a sump pump or similar device. The various components of the leachate collection and removal system will also need to be maintained periodically. This level of human activity over long periods of time is impractical.

The permanent isolation barrier is intended to remain functional throughout its design life without human intervention. Consequently, in designing a permanent isolation barrier, it has been important to understand the natural processes that are expected to act on the barrier during its design life. Knowledge of how natural processes affect barrier performance has resulted in a design that passively meets design and performance objectives.

F.4 Results of Barrier Development Program Research

During the period from 1986 through 1990, laboratory and field research efforts were undertaken by the BDP. The results of this research and findings to date are briefly summarized below:

F.4.1 Water Intrusion Control

At the Field Lysimeter Test Facility (FLTF) and the Small Tube Lysimeter Facility (STLF), studies are under way to quantify water balance under conditions that are currently found at Hanford waste sites and under conditions that may exist when surface isolation barriers are emplaced (Gee et al. 1989; Campbell et al. 1990; Campbell and Gee 1990; Sackschewsky et al. 1991; Waugh et al. 1991). These lysimeter studies are perhaps the most precise water balance studies conducted at an arid site to date.

F.4.1.1 Field Lysimeter Test Facility

Constructed in 1987, the FLTF consists of 14 large-diameter drainage-type lysimeters 3-m (9.8-ft) and 1.5-m (4.9-ft) deep, weighing lysimeters, and 6 additional clear plastic lysimeters (Gee et al. 1989; Campbell et al. 1990; Campbell and Gee 1990). Seven barrier treatment alternatives are being evaluated in this program. These alternatives all rely on a soil textural break to provide the infiltration barrier based on the outflow law for soil water proposed by Richards (1950). The outflow law limits the percolation of water from a fine-textured soil, which exhibits a high capillary pressure, to a coarse-grained, clean sand or gravel, which exhibits a very low capillary pressure; as a result, moisture will be retained in the overlying, fine-textured soil until the water content in the soil approaches saturation. The observations in the FLTF lysimeters demonstrate the need for at least a 1-m (3.3-ft) upper layer of fine soil with surface vegetation to enhance evapotranspiration. If vegetation is absent and a substantial sand or gravel layer is on the surface, precipitation has penetrated deeply and eventually drained through these lysimeters.

Through lysimeter experiments and modeling it has been shown that the silt-loam soil profile will recycle two and three times the normal precipitation from either vegetated or vegetation-free sites (Cadwell 1991; Waugh et al. 1991). Thus, for both natural fine soil (i.e., silt) profiles and a protective barrier using fine soils, virtually no net recharge would occur, and the currently used limit for recharge of 0.1 cm/yr (0.04 in.) or less could be applied indefinitely (Fayer et al. 1985; Fayer 1987; Fayer, Rockhold and Holford 1992).

F.4.1.2 Plant Transpiration/Evapotranspiration

In 1989 and 1990 the evaporation, evapotranspiration, and carbon dioxide exchange rates for the McGee silts were obtained with and without cheatgrass for use in water balance models. Once again, it was shown that vegetation significantly reduces water penetration and can be effective in preventing drainage (Link et al. 1990; Link et al. 1992a, 1992b).

F.4.1.3 Diversion Barrier Testing

Using the STLTF, the effectiveness of asphalt and clay/grout barriers is being evaluated. To date, all of these barrier systems have prevented surface moisture from passing through the lysimeters (Freeman and Gee 1989a, 1989b; Relyea, Sackschewsky and Waugh 1989).

F.4.2 Biointrusion Control

One or more components of the prototype barrier should be an effective deterrent to animal burrowing and root intrusion. Evaluations of animal burrowing and root intrusion impacts on protective barriers are being conducted to determine parameters on the extent and nature of burrowing and intrusion that occur during the life of the barrier.

F.4.2.1 Small Mammal Intrusion Studies

An animal intrusion lysimeter facility (AILF) was constructed in 1988 to assess the effects of small mammal burrows on the infiltration of precipitation through soil layers such as may be used in the barrier. Data from lysimeter tests completed thus far indicate that no significant differences occurred in the water content at depth in soils with and without burrows. Additionally, the maximum depth of burrow penetration always exceeded 122 cm (4 ft) and typically reached the bottom of the lysimeters (Landeem 1990, 1991).

F.4.2.2 Large Mammal Intrusion Studies

Measurements obtained in 1989 and 1990 indicate that during natural rainfall, precipitation penetrates deeper beneath and adjacent to badger burrows. However, enhanced evapotranspiration in the proximity of the burrows leads to a rapid loss of this moisture (Cadwell, Eberhardt and Simmons 1989).

F.4.2.3 Root Intrusion Studies

Vegetation will function as an important component of the protective barrier, both to stabilize the soil surface and to extract soil moisture from the soil and recycle it to the atmosphere through evapotranspiration. For the prototype barrier design, in which fine soils overlie graded layers, the optimal root distribution for barrier function will be one in which roots fully exploit the fine-soil layer. However, the establishment and growth of deep-rooted plants on the barrier presents the possibility of intrusion of plant roots into the wastes and subsequent biotic transport of hazardous materials.

Based on limited small-diameter soil and root cores obtained in 1990, it was observed that grass roots dominate the upper 20 cm (8 in.) of the soil, while shrub roots dominate the soil below this level. The deepest penetrating roots (tumbleweeds) would extend to a depth of 100 cm (3.3 ft), which is well into the typical buried waste site, if an effective root barrier is not employed.

F.4.3 Erosion/Deposition Control

Erosive stresses on the 200 Area plateau of the Hanford Site will impact actual waste site barriers. The BDP is conducting research to 1) monitor the surface layer as it ages under exposure to natural conditions; 2) measure actual rates of surface deflation or inflation; 3) obtain micro-meteorological information about erosive, or shear, stresses that impact the barrier; 4) obtain information about abrasive sand particle scouring (saltation); 5) create a sand dune and monitor the impact on surface erosion, plant community viability, and soil reservoir water balance; and 6) study erosive impacts after an artificial wildfire removes all surface vegetation.

F.4.3.1 Field Study of Gravel Admixture, Vegetation, and Soil

Six field plots were constructed in 1986 to evaluate the effect of varying surface treatments on plant growth and resistance to wind and water erosion. The data indicate that the gravel admixture does not limit vegetative growth or lead to an increase in the soil moisture beneath the admixture (Last et al. 1987; Waugh 1989; Waugh et al. 1990).

F.4.3.2 Small-Tube Lysimeter Tests

The small-tube lysimeter facility (STLF), containing 105 lysimeters, was constructed in 1988 to evaluate root penetration depth and infiltration from alternate erosion-resistant surfaces. Significant among the observations was the finding that a gravel surface with no vegetation will lead to significant infiltration of precipitation, regardless of the soil type underlying the gravel (Relyea, Sackschewsky and Waugh 1989; Sackschewsky et al. 1991).

F.4.3.3 Wind Erosion

Wind tunnel studies performed in 1990 indicated that the McGee silts are subject to significant deflation unless stabilized by vegetation or a gravel/soil cover. The addition of 15% to 30% pea gravel to the native surface silts halted wind erosion by providing a surface armor that simulates naturally occurring desert pavement (Ligotke 1988; Ligotke and Klopfer 1990).

F.4.3.4 Water Erosion

Small plots equipped with run-off flumes were tested at the McGee Ranch to demonstrate the effectiveness of the gravel admixtures in limiting erosion of the silts. Preliminary results indicate that the admixture reduces raindrop-splash induced erosion (Walters, Hoover and Cadwell 1990; Hoover, Cadwell and Walters 1990).

Erosion studies have shown that soil surfaces, once armored with rock, resist further erosion under the influence of arid or semi-arid climates. The surface soil of the Hanford Protective Barrier is designed to include a rock fraction, i.e., a pea-gravel admixture. Thus, if and when wind erosion removes the fine soils at the surface, a rock armoring will remain as a surface armoring to preclude further wind erosion. The nominal thickness of rock armoring required to defeat the wind erosion process is estimated to be 2 rock diameters or a maximum of 10 cm (3.9 in.). Conservatively, it is estimated that wind erosion may remove between 10 and 50 cm (3.9 and 19.7 in.) of fine soil during the creation of the armor surface. The creation of a desert pavement surface will leave at least 1.5 m (4.9 ft) of fine soil; an amount research has shown is ample to minimize infiltration into waste sites at arid sites such as Hanford.

F.4.4 Summary

These studies have aided in the selection of the cover materials and the quantification of water balance for a combination of selected soil-layer sequences. The deposit of silt-loam soil at the McGee Ranch location on the Hanford Site has been identified as the source of material for the fine soil. Sand and gravel filter layers have been identified as essential to prevent the migration of the fine soil into the pore space of the basalt rip-rap. An asphalt subsurface layer is currently proposed as a redundant water diversion that would prevent drainage of water below the multilayered soil barrier system for a thousand years or more.

F.5 Intrusion and Land Use Scenarios

F.5.1 Short-Term Human Intrusion Scenarios after Institutional Control

Markers will be placed in the protective barrier to warn those who would, for any reason, disturb the buried wastes (Adams and Kaplan 1986; Kaplan and Adams 1986). Absolute assurance can not be given that future generations would understand the warning or adhere to it. Thus, human intrusion scenarios may develop regarding the materials that comprise the protective barrier. Earthen materials in the barrier that have intrinsic value to society include the surface gravels (included in the surface soil to provide armoring), the silt-loam soil, and the underlying coarse rock. Possible scenarios include the following:

- *Gravels or Basalt Rock as a Commodity of Interest:* Consider the removal of surface gravel, wind erosion of the silt-loam, eventual exposure of the coarse gravels and basalt rip-rap, and removal of this coarse material. If this scenario is credible, it requires one of two approaches: 1) completely ignore the presence of the protective barrier and simply assume a backfill soil surface, or 2) develop a complex sequence of infiltration rates corresponding to the exposed surface material. Complete removal of surface and deeper gravel materials is believed to be highly unlikely; it is more likely that gravels and rock would be acquired from other abundant natural deposits on the Hanford Site.

If the coarse material were removed, the redundant layer of asphalt placed at depth beneath the barrier provides an extra measure of protection. Until such time as the asphalt would biodegrade, assume a thousand years, this secondary infiltration barrier would act to divert direct infiltration. The study of asphalt layers for secondary protection in the barrier design is currently under way (Freeman, Gee and Relyea 1989; Freeman and Gee 1989b). This asphalt would be below the land surface and would not be exposed to daily or seasonal climate variations, thus the biodegradation rate is assumed to be the same as for the asphalt pavement surrounding the vault.

- *Silt-Loam Soils as a Commodity of Interest:* Consider the removal of the 2-m- (6.6-ft-) thick silt-loam surface deposit, and the exposure of underlying coarse gravels and basalt. If this

were to occur soon after the loss of institutional control, the waste underlying the disturbed portion of the barrier would be exposed to greatly enhanced recharge over its entire disposal period. A relatively thick layer of coarse gravel acts as a recharge basin; thus, infiltration through the gravel could result in drainage of a significant portion of the annual (~16-cm/yr; 6.3-in./yr) precipitation (Smoot et al. 1989). The underlying redundant asphalt layer(s) would then function as the primary barrier to high recharge rates. The study of asphalt degradation under the Hanford Grout Technology Program has led to assumed biodegradation of the asphalt-concrete diffusion barrier; therefore, asphalt within the isolation barrier is also assumed to biodegrade. Thus, direct leaching of the waste at high recharge rates could occur after approximately 1,000 years. Another key aspect to such a scenario would be the area or portion of the barrier surface assumed to be mined by the intruder.

- *Agricultural Use of the Barrier Surface:* consider the practice of agriculture on the silt-loam soils. The nature of future agricultural practice must be assumed (i.e., whether erosion would be controlled, likely crops, whether and how irrigation would be applied). All of this must be assumed before arriving at expected values for recharge. Under this scenario, the underlying asphalt would function as the primary barrier to net recharge past the waste form.

F.5.2 Long-Term Scenarios

Long-term scenarios range from a) pre-Hanford conditions with irrigated agriculture along the river and natural range land at and above the 200 Area plateau, to b) extensive irrigated agriculture throughout what is presently the Hanford Site. The role that water rights could play in the source and availability of water is unknown. The role that wildlife refuges may play is also unknown. Protection of the natural environment along the Hanford Reach of the Columbia River resulting from the declaration of a scenic river area is currently being debated.

The present agricultural development of lands surrounding the Hanford Site and the proximity of these lands to sources of water (e.g., the Columbia River and underlying basalt aquifers) contribute to a high likelihood of agricultural development of Hanford after the Site is returned to the public domain. Because very long-term institutional control cannot be assumed, one can assume that agricultural development will encroach upon the waste deposits in the 200 Area Plateau. One could even assume that the surface of the protective barrier would be farmed.

Regardless, the issue of long-term future land use seems to revolve around two options: 1) natural recharge of an environment even if precipitation triples, and 2) irrigated agriculture that would apply significantly greater amounts of water. It is uncertain that current irrigation practices could be sustained for the indefinite future, i.e., thousands of years. However, irrigation practices will evolve and with the rotation of crops and evolution of agricultural practices, it is conceivable that some form of agriculture would be conducted over the long term at Hanford.

Findings of the barrier research program are that fine-soil profiles protect indefinitely against recharge even with up to twice the current precipitation rate. This is true for natural (e.g., layered) and disturbed silt profiles, and for cases with or without vegetation. Thus, if natural precipitation is used in a dry-land farming scenario, one can conclude minimal long-term recharge. If, however, irrigation is applied according to current practices, the surface soil and vegetation/crop capacity for storing and recycling water potentially could be overwhelmed, and significant amounts of recharge should be assumed. Future irrigation methods are unknown, however, the trend is toward localized irrigation (e.g., drip irrigation), and therefore, recharge through the silt-loam surface soil of the protective barrier could be assumed to be minimal for the long-term future. Salt build up in soils is prevented by applying sufficient irrigation to both supply the crop requirement and leach salts down into the soil profile and away from the root zone. Elsewhere on the Hanford Site, where silt soil profiles are not present at the land surface, greater amounts of recharge should be assumed to correspond to future irrigation scenarios.

F.6 Estimates Of Recharge

Bauer and Vaccaro (1990) estimated groundwater recharge for the Hanford Site as part of their study of recharge affecting the Columbia Plateau regional aquifer. Using daily precipitation and temperature data for the period 1956 through 1977, and a water budget model, they estimated recharge for subareas of the Hanford Site ranging in size from 0.25 to 1.0 mi². Their model included the following physical processes: snow accumulation and melt, interception of precipitation, surface runoff, evaporation from foliar cover, evaporation from bare soil, and plant transpiration. It accounts for the influences of soil type, land use, plant growth, altitude, slope and aspect. The long-term (i.e., 21-year) average of annual recharge for the entire Hanford Site was estimated to be 0.97 cm/yr (0.38 in./yr). They estimated a long-term average recharge rate of 0.25 to 1.3 cm/yr (0.1 to 0.5 in./yr) at the location of the grout facility on the 2(X) Area plateau.

Routson and Johnson (1990) reviewed water infiltration data from a 13-year period of observation for a closed-bottom lysimeter located in the 2(X) East Area, and ¹³⁷Cs profile data from a solid waste burial ground trench in the 2(X) West Area. They concluded that for the natural soils and vegetation of the 2(X) Area plateau and for areas where natural near-surface conditions could be restored, there is very little potential for downward movement of contaminants in the upper vadose zone. The recharge rate of the closed-bottom lysimeter was estimated to be 0.0 ± 2 mm/yr based on the 13-year record. They recommended that management and cleanup efforts strive to maintain or recreate natural soil and vegetative cover conditions.

Gee et al. (1992) reviewed all published recharge studies for Hanford and described the reasons for highly variable observations of recharge. They describe the roles played by the three major factors of climate, soil, and vegetation. Clearly, recharge is directly related to annual precipitation; where recharge is observed, more precipitation implies more recharge. Recharge has also been shown to depend on the seasonal distribution of precipitation, with maximum recharge events occurring after the wettest winter

periods. Recharge is greatest for coarse-textured soils; least for fine-textured soils. It is greatest for surfaces that are maintained free of vegetation; least for surfaces supporting both shallow- and deep-rooted vegetation.

The lysimeter studies at Hanford show for present climate conditions [i.e., 160-mm (6.3-in.) annual average precipitation], as well as for accelerated precipitation [up to 320 mm/yr (12.6 in./yr) or more], that surface barriers consisting of more than 1 m (3.3 ft) of fine (i.e., silt or silt-loam) soil over coarse subsurface materials are capable of preventing water from draining into underlying soils or wastes. Gee et al. (1992) reported results obtained on the 200 Area plateau at the Hanford Site from lysimeters containing silt loam. Lysimeters that were exposed to two times (2x) normal precipitation from 1987 through 1990 produced no drainage regardless of the presence or absence of plants. Unpublished data from continued monitoring of these lysimeters, which have since been subjected to an excess of three times (3x) normal precipitation, reveal no drainage from vegetated lysimeters but drainage through lysimeters maintained free of vegetation. The studies have shown that deep-rooted sagebrush and tumbleweed plants are more efficient than shallow-rooted cheatgrass in removing soil water from a soil profile. All lysimeters with vegetation exhibit a greater ability to recycle water to the atmosphere than do bare-soil lysimeters. All of this suggests that a 1-m (3.3-ft) deposit of silt soil is ideally suited to limit water infiltration under the semiarid conditions of vegetation and climate at Hanford. It has also been shown that creating an armored desert pavement by adding a gravel mix to the surface deposit of silt protects the barrier from potential eolian erosive forces and does not degrade the water cycle performance of the barrier (Vaughn et al. 1990).

The design of the protective barrier accounts for the potential of wind erosion by incorporating gravel admix in the upper silt layer. The potential for deposition of wind-blown soils is now being addressed by the barrier program. Dunes cover a significant portion of the Hanford Site, and are predominantly a fine sand. The majority of these dunes, which lie to the south and southeast of the Grout Disposal Facility, are vegetated to some extent, and recharge is expected to be low where vegetation is present (Gee et al. 1992) but recharge has not been measured directly on the dune areas. At present, the more active and least vegetated dunes lie to the southeast of the facility adjacent to the Columbia River. It is probable that shallow-rooted vegetation is better able than deep-rooted species to adapt to the dynamic active dune environment. As a result, infiltration and recharge at active dune locations could be a substantial fraction of the precipitation. However, the present location of dunes, being south and southeast and downwind of the Grout Disposal Facility, make it less probable that dune formation (deposition) events will dominate the future and more probable that wind erosion events will dominate.

The results of research reported by Gee et al. (1992) are more relevant to the surface barrier because it involves silt loam soils, vegetation, and climate specific to the barrier design and 200 Area plateau. Thus, the interpretation of field observations and supporting simulations of the near-surface environment, that there will be negligible or nonmeasurable recharge through an isolation barrier, is adopted.

The net infiltration design goal for the permanent isolation barrier is 0.05 cm/yr (0.02 in.) (i.e., a non-zero value), because the field measurement program could not achieve an absolute zero recharge goal. This value could have been adopted as the infiltration rate for the performance assessment analysis; however, it was doubled and the value 0.1 cm/yr (0.04 in./yr) was adopted to provide additional conservatism.

F.7 References

- Adams, M. R. and M. F. Kaplan. 1986. "Marker Development for Hanford Waste Site Disposal." In R.G. Post (ed.), *Waste Management '86* (Vol. 1), pp. 425-431, University of Arizona, College of Engineering and Mines, Tucson, Arizona.
- Adams, M. R., and N. R. Wing. 1986. *Protective Barrier and Warning Marker System Development Plan*. RHO-RE-PL-35 P, Rockwell Hanford Operations, Richland, Washington.
- Bauer, H. H. and J. J. Vaccaro. 1990. *Estimates of Ground Water Recharge to the Columbia Plateau Regional Aquifer System; Washington, Oregon and Idaho for Predevelopment and Current Land Use Conditions*. WRIR 88-4108, U.S. Geological Survey, Tacoma, Washington.
- Cadwell, L. L. (ed.). 1991. *Hanford Site Protective Barrier Development Program: Fiscal Year 1990 Highlights*. PNL-7831, Pacific Northwest Laboratory, Richland, Washington.
- Cadwell, L. L., L. E. Eberhardt, and M. A. Simmons. 1989. *Animal Intrusion Studies for Protective Barriers: Status Report for FY 1988*. PNL-6869, Pacific Northwest Laboratory, Richland, Washington.
- Campbell, M. D., G. W. Gee, M. J. Kanyid, and M. L. Rockhold. 1990. *Field Lysimeter Test Facility: Second Year (FY 1989) Test Results*. PNL-7209, Pacific Northwest Laboratory, Richland, Washington.
- Campbell, M. D., and G. W. Gee. 1990. *Field Lysimeter Test Facility: Protective Barrier Test Results (FY 1990, the third year)*. PNL-7558, Pacific Northwest Laboratory, Richland, Washington.
- Fayer, M. J. 1987. *Model Assessment of Protective Barrier Designs: Part II*. PNL-6297, Pacific Northwest Laboratory, Richland, Washington.
- Fayer, M. J., W. Conbere, P. R. Heller, and G. W. Gee. 1985. *Model Assessment of Protective Barrier Designs*. PNL-5604, Pacific Northwest Laboratory, Richland, Washington.
- Fayer, M. J., M. L. Rockhold, and D. J. Holford. 1992. *Model Assessment of Protective Barriers: Part III Status of FY 1990 Work*. PNL-7975, Pacific Northwest Laboratory, Richland, Washington.
- Freeman, H. D., G. W. Gee, and J. F. Relyea. 1989. *Field Study Plan for Alternate Barrier*. PNL-6840, Pacific Northwest Laboratory, Richland, Washington.

Freeman, H. D., and G. W. Gee. 1989a. *Hanford Protective Barriers Program Asphalt Barrier Studies - FY 1988*. PNL-6874, Pacific Northwest Laboratory, Richland, Washington.

Freeman, H. D. and G. W. Gee. 1989b. *Hanford Protective Barriers Program: Status of Asphalt Barrier Study - FY 1989*. PNL-7513, Pacific Northwest Laboratory, Richland, Washington.

Gee, G. W., L. L. Cadwell, H. D. Freeman, M. W. Ligothke, S. O. Link, R. A. Romine, and W. H. Walters, Jr. 1993. *Testing and Monitoring Plan for the Permanent Isolation Surface Barrier Prototype*. PNL-8391, Pacific Northwest Laboratory, Richland, Washington.

Gee, G. W., M. J. Fayer, M. L. Rockhold, and M. D. Campbell. 1992. "Variations in recharge at the Hanford Site." *Northwest Science* 66(4):237-250.

Gee, G. W., R. R. Kirkham, J. L. Downs, and M. D. Campbell. 1989. *The Field Lysimeter Test Facility (FLTF) at the Hanford Site: Installation and Initial Tests*. PNL-6810, Pacific Northwest Laboratory, Richland, Washington.

Hoover, K. A., L. L. Cadwell, and W. H. Walters. 1990. *Hanford Protective Barriers Program: Water Erosion Studies - FY 1989*. PNL-7214, Pacific Northwest Laboratory, Richland, Washington.

Kaplan, M. F. and M. R. Adams. 1986. "Using the Past to Protect the Future: Marking Nuclear Waste Disposal Sites." *Archeology* 39(5):51-54.

Landeen, D. S. 1990. *Animal Intrusion Status Report for Fiscal Year 1989*. WHC-EP-0299, Westinghouse Hanford Company, Richland, Washington.

Landeen, D. S. 1991. *Animal Intrusion Status Report for Fiscal Year 1990*. WHC-EP-0398, Westinghouse Hanford Company, Richland, Washington.

Last, G. V., M. A. Glennon, M. A. Young, and G. W. Gee. 1987. *Protective Barrier Materials Analysis: Fine Soil Site Characterization*. PNL-6314, Pacific Northwest Laboratory, Richland, Washington.

Ligothke, M. W. 1988. *Soil Erosion Rates from Mixed Soil and Gravel Surfaces in a Wind Tunnel: A Preliminary Report*. PNL-6677, Pacific Northwest Laboratory, Richland, Washington.

Ligothke, M. W., and D. C. Klopfer. 1990. *Soil Erosion Rates from Mixed Soil and Gravel Surfaces in a Wind Tunnel*. PNL-7435, Pacific Northwest Laboratory, Richland, Washington.

Link, S. O., J. L. Downs, M. E. Thiede, D. J. Lettau, T. R. Twaddell, and R. A. Black. 1992a. *Evapotranspiration Studies for Protective Barriers: FY 1990 Status Report*. PNL-8032, Pacific Northwest Laboratory, Richland, Washington.

Link, S. O., M. E. Thiede, J. L. Downs, D. J. Lettau, and W. J. Waugh. 1992b. *Evapotranspiration Studies for Protective Barriers: FY 1989 Status Report*. PNL-8033, Pacific Northwest Laboratory, Richland, Washington.

Link, S. O., M. E. Thiede, R. D. Evans, J. L. Downs, and W. J. Waugh. 1990. *Evapotranspiration Studies for Protective Barriers: FY 1988 Status Report*. PNL-6985, Pacific Northwest Laboratory, Richland, Washington.

Phillips, S. J., M. R. Adams, T. W. Gilbert, C. C. Meinhardt, R. M. Mitchell, and W. J. Waugh. 1985. *Engineered Barrier Test Facility Status Report: 1984*. RHO-WM-SR-3P, Rockwell Hanford Operations, Richland, Washington.

Relyea, J. F., M. R. Sackschewsky, and W. J. Waugh. 1989. *Small-Tube Lysimeter Facility Status Report for Fiscal Year 1989*. WHC-EP-0297, Westinghouse Hanford Company, Richland, Washington.

Richards, L. A. 1950. "Laws of soil moisture." *Transactions American Geophysical Union* 31:750-756.

Routson, R. C., and V. G. Johnson. 1990. "Recharge estimates for the Hanford Site 200 Areas Plateau." *Northwest Science* 64(3):150-158.

Sackschewsky, M. R., C. J. Kemp, L. L. Cadwell, M. E. Thiede, and W. J. Waugh. 1991. *Status Report for the Small-Tube Lysimeter Facility Fiscal Year 1990*. WHC-EP-0381, Westinghouse Hanford Company, Richland, Washington.

Smoot, J. L., J. E. Szecsody, B. Sagar, G. W. Gee, and C. T. Kincaid. 1989. *Simulations of Infiltration of Meteoric Water and Contaminant Plume Movement in the Vadose Zone at Single-Shell Tank 241-T-106 at the Hanford Site*. WHC-EP-0332, Westinghouse Hanford Company, Richland, Washington.

U.S. Environmental Protection Agency (EPA). 1990. *Seminars--Design and Construction of RCRA/CERCLA Final Covers*, Center for Environmental Research Information 90-55, U.S. Environmental Protection Agency, Office of Research and Development, Washington, D.C.

U.S. EPA. 1982. *RCRA (Resource Conservation and Recovery Act) Guidance Document: Landfill Design. Liner Systems and Final Cover*. PB87-157657, National Technical Information Service, Springfield, Virginia.

Walters, W. H., K. A. Hoover, and L. L. Cadwell. 1990. *Project Test Plan for Runoff and Erosion on Fine-Soil Barrier Surfaces and Rock-Covered Side Slopes*. PNL-6791, Pacific Northwest Laboratory, Richland, Washington.

Waugh, W. J. 1989. *Gravel Admix, Vegetation and Soil Water Interactions in Protective Barriers: Experimental Design, Construction and Initial Conditions*. PNL-6616, Pacific Northwest Laboratory, Richland, Washington.

Waugh, W. J., M. E. Thiede, L. L. Cadwell, G. W. Gee, H. D. Freeman, M. R. Sackschewsky, and J. F. Relyea. 1991. In R. G. Allen (ed.), "Small lysimeters for documenting arid site water balance." *Proceedings of the International Symposium on Lysimetry*, Amer. Soc. Civil Engr., New York. pp. 151-159.

Waugh, W. J., M. E. Thiede, C. J. Kemp, L. L. Cadwell, and S. O. Link. 1990. *Field Study of Gravel Admix, Vegetation, and Soil Water Interactions: Protective Barrier Program Status Report - FY 1989*. PNL-7440, Pacific Northwest Laboratory, Richland, Washington.

Wing, N. R. September 1992. *A Peer Review of the Hanford Site Permanent Isolation Surface Barrier Development Program*. WHC-MR-0392. Westinghouse Hanford Company, Richland, Washington.

Wing, N. R., L. L. Cadwell, J. W. Cammann, J. C. Chatters, M. J. Fayer, H. D. Freeman, G. W. Gee, L. S. Hermann, M. W. Ligothe, D. R. Myers, K. L. Petersen, J. C. Sonnichsen, W. H. Walters, and M. Warn. August 1992. *Permanent Isolation Surface Barrier and Warning Marker System Development Plan*. WHC-AA-XXXX, Westinghouse Hanford Company, Richland, Washington.

Appendix G

Detailed Description of PORFLOW

Appendix G

Detailed Description of PORFLOW

M. G. Piepho and F. M. Mann, Westinghouse Hanford Company

G.1 Selection of PORFLOW

The criteria for selecting the PORFLOW code included consideration of the code's theoretical framework, implementation of the theory, documentation, quality control, acceptability by the technical community, and computation speed. The first criteria is that the theoretical framework be based on appropriate fundamental principles of chemistry and physics (e.g., continuity). The theoretical framework of PORFLOW is based on appropriate fundamental principles of chemistry and physics and well-established constitutive equations. The second criteria, which is related to the first, is that implementation of theory in the code be applicable to the problem being addressed. Overall, PORFLOW is applicable to problems of unsaturated flow in dry soils. Specific modifications were made to the code allowing simulation of degradation changes to engineered barriers to make a version (2.394gr) applicable for use in the grout performance assessment (Piepho et al. 1993). The primary code changes were to allow continuous time-dependent diffusion coefficients and the capability to model changes in hydraulic/transport properties (for example, saturated conductivities, moisture retention curves, partition coefficients) over time during one run.

The third and fourth criteria for selection were related to documentation of the code and quality assurance. Sufficient documentation must exist to describe the theoretical framework, computational techniques, and user interaction with the code (including examples). The framework and computational techniques for PORFLOW version 1.0 are documented in a WHC report (Sagar and Runchal 1990), while a user manual (Runchal and Sagar 1992) exists for version 2.40. (Version 2.40 is essentially the same as version 2.394gr.) The primary change in version 2.394gr was allowance of a time-dependent diffusion coefficient for asphalt, a feature that increases the diffusion coefficient of the asphalt-concrete barrier by six orders of magnitude (10^{-10} to 10^{-4} cm²/s) over 90,000 years. Other changes include the ability to change hydraulic properties (saturated conductivity, porosity, moisture retention parameters, etc.) between SOLVE commands without having to restart.

To fulfill the requirements of quality assurance, the code selected must have a verification report for the version used and be under configuration control. A number of verification and benchmarking efforts for version 2.394gr have been performed (Piepho et al. 1993). In addition, version 1.0 was

verified and benchmarked by Magnuson et al. (1990). Using the same procedures that were used for version 1.0, PORFLOW version 2.4 was verified and benchmarked as part of the performance assessment being prepared for the Savannah River Site Saltstone Disposal Facility.^(a)

The fifth criteria is acceptance of the code by the technical community. The PORFLOW family of codes has been used extensively across the DOE complex. Version 1.0 of the PORFLO-3 code, an earlier version of the code, has been used at the Idaho National Engineering Laboratory to model a large organic vapor plume (Baca et al. 1988) and to model concrete barriers (Walton and Seitz 1991). In addition, as stated above, version 2.4 was used for the Savannah River performance assessment that is currently being prepared. At the Hanford Site, PORFLOW has been used many times, including applications for the Basalt Waste Isolation Project (U.S. DOE/RL 1982 and Baca et al. 1984), simulations of a single-shell tank leak (Smoot and Sagar 1990), evaluation of liquid effluent discharges from 200 Area cribs (WHC 1990), a preliminary single-shell tank performance assessment (Sonnichsen 1991), a study of effluent disposed to trenches in the 100-N Area (Connelly et al. 1991), and a comparison of three methods for solving flow equations (Piepho and Runchal 1991). PORFLOW was also selected to be one of three codes to be used for modeling performed under the Federal Facilities Agreement and Consent Order (i.e., the Tri-Party Agreement) between the U.S. Department of Energy, the U.S. Environmental Protection Agency, and the Washington Department of Ecology (U.S. DOE/RL 1991). Validation exercises have been performed with an older version of PORFLOW for simulation of flow and transport at an experimental trench in Las Cruces, New Mexico (Wittmeyer and Sagar 1992a,b and Rockhold and Wurster 1991). The newer version (2.394gr) of PORFLOW has been able to repeat all test calculations that the older version has done, including the Las Cruces trench case (Piepho et al. 1993). All the cases used for grout are discussed and shown by Piepho (1993).

The sixth criteria is sufficient computational speed of the code to allow a simulation to be solved in a reasonable length of time. Because of the complexity of the simulations and the lengthy time scales being analyzed in this performance assessment (up to one million years), the PORFLOW code requires many hours of CRAY time. The codes TRACR3D (Travis 1984) and S301-2 (Farmer 1984), which were used in a previous evaluation of grout performance assessment, were slower and were used only for benchmarking in the current effort.

G.2 History of PORFLOW Version 2.394gr

The original version of PORFLOW (Kline et al. 1983 and Runchal et al. 1985), limited to saturated conditions in two-dimensional porous domains, was extensively verified and benchmarked by Eyler and Budden (1984) and also by Runchal et al. (1985). The code was extended to model variably saturated

(a) McDowell-Boyer, L. Preliminary Predecisional Draft of Saltstone Disposal Facility Performance Assessment. Letter transmitting the SRS performance assessment to the Peer Review Panel. Oak Ridge National Laboratory, August 6, 1992.

flow in three-dimensional geometry and was termed PORFLO-3, version 1.0 (Runchal and Sagar 1989, Sagar and Runchal 1990). A newer version able to treat multiphase problems (2.1) was developed for DOE and is the basis of the version used in this performance assessment. A commercially available version of PORFLOW version 2.41 (Runchal and Sagar 1992) was released in August 1992. Version 2.394 of PORFLOW was released in November 1991 and is the starting point for the special version 2.394gr tailored for use in this work (Piepho et al. 1993).

G.3 Theoretical Framework

G.3.1 Governing Equations and Assumptions

The equations solved in PORFLOW are based on the conservation principles of continuum mechanics. These equations describe fluid flow and mass transport processes in heterogeneous and anisotropic porous media. The equations are well accepted mathematical representations and are found in such standard texts as Bear and Bachmat (1990), Freeze and Cherry (1979), and Huyakorn and Pinder (1983). The specific partial differential equation solved in PORFLOW for isothermal fluid flow around and through the grout disposal facility is

$$S_e \frac{\partial P}{\partial t} = \frac{\partial}{\partial x_i} \left(K_{ij} \frac{\partial P}{\partial x_j} \right) + m_v$$

where S_e = fluid storage term (i.e., specific storage or moisture capacity term)

P = piezometric head (i.e., total hydraulic head)

K_{ij} = hydraulic conductivity tensor

m_v = fluid volume source or sink term

t = time

x_i = distance in the i th direction.

The quantity P is defined by

$$P = h + z - z^*$$

where h = pressure head (capillary pressure head)

z = elevation head

z^* = reference value

and the quantity S_e is defined by

$$S_e = S(\alpha_s + \theta_e \alpha_f) + \theta_e \frac{\partial S}{\partial p}$$

where S = saturation level

α_s = solid compressibility normalized by the specific weight of the fluid

α_f = fluid compressibility normalized by the specific weight of the fluid

θ_e = effective porosity.

Some of the basic assumptions made in the above mathematical formulations are

1. the fluid flow is laminar, slightly compressible, and single phase
2. the fluid flow obeys Darcy's law for porous flow
3. fluid viscosity is a function of temperature only
4. the hydraulic properties of the porous continuum are volume averages
5. osmotic effects (associated with the waste form) are negligible.

In general, these assumptions are satisfied in the hydrogeologic environment of the grout vaults except for assumption 5. The osmotic effects of grout are not modeled explicitly. Vapor return effects have been modeled by introducing a liquid water source, which represents the condensed vapor, at any exposed grout interfaces.

The specific partial differential equation solved in PORFLOW for contaminant transport from the grout vault is

$$R_f \phi_D \frac{\partial C}{\partial t} + \frac{\partial}{\partial x_i} (V_i C) = \frac{\partial}{\partial x_i} \left[\Gamma_{ij}^C \frac{\partial C}{\partial x_j} \right] - \phi_D R_f \lambda C + S_C + \sum_p \phi_D R_f^p \sigma^p \lambda^{mp} C$$

where C = contaminant concentration

V_i = Darcy velocity in i^{th} direction

R_f = retardation factor

Γ_{ij}^C = hydrodynamic dispersion tensor

λ = decay rate

S_C = mass source term

σ^p = fraction of decay of the parent mass species which generates the current species, and the superscript p refers to the parent mass species.

The last term in the above equation represents the ingrowth of mass species. The retardation factor R_f is defined by

$$R_f = \left[1 + (1 - \theta_T) \frac{\rho_s R_d}{\theta_D} \right]$$

where ρ_s = solid (particle or grain) density

θ_T = total porosity

θ_D = total diffusive porosity

R_d = sorption (distribution) coefficient. (denoted by K_d in many other reports)

and Γ_{ij}^C is defined (Kemper and van Schaik 1966) by

$$\Gamma_{ij}^C = \alpha D_M \exp (b\phi_D)$$

where ϕ_D = effective diffusive pore space saturated with water, (i.e., effective diffusive moisture content)

D_M = molecular diffusion coefficient

a,b = parameters (the "a" parameter can include tortuosity).

All other coefficients are as previously defined. The Kemper diffusion model is optional in PORFLOW and was the choice for the grout performance assessment.

Some of the key assumptions that limit the applicability of the above formulation are as follows:

1. contaminant concentrations are low enough that the fluid flow is independent of mass transport, i.e., concentrations do not affect the density or viscosity of the fluid
2. diffusion of the contaminants through the fluid obeys Frick's first law
3. adsorption (and desorption) of contaminants into the porous medium is an equilibrium process described by a linear isotherm.

The model formulation is applicable to both saturated and unsaturated flow conditions.

G.3.2 Initial and Boundary Conditions

The PORFLOW code accommodates the specification of standard mathematical boundary conditions. These include

1. Dirichlet (fixed head or concentration)
2. Neumann (specified flux)
3. Robin (mixed).

Detailed information on boundary conditions is given in Runchal and Sagar (1989 and 1992).

G.3.3 Numerical Techniques

In PORFLOW, the governing equations for flow and transport are solved using a method referred to as the Nodal Point Integration, a variation of the finite volume or integrated finite difference technique. In this method, the difference approximations to the governing equations are derived on a staggered grid system. The state variables are computed at the grid nodes whereas the fluid velocities and fluxes are computed at the cell faces (located midway between adjacent grid nodes). Three discretization schemes, or basis functions to be integrated, are provided. The user may select which of the three schemes is to be used to maximize accuracy and stability.

The system of algebraic equations produced by the finite volume are solved using one of five techniques:

1. point successive overrelaxation
2. alternating direction implicit (ADI)
3. Cholesky decomposition
4. Gauss elimination
5. reduced system conjugate gradient method.

The nonlinearity of the governing equation for variably saturated flow is solved using a Picard iteration method. The ADI was the method used for all of the grout PA runs, since it has been very robust in previous work.

G.4 Code Inputs And Outputs

G.4.1 Input Data Structure

PORFLOW uses a free-form input which allows the user to document the input data deck. The input file uses a keyword approach to define primary input data groups. For typical flow and transport simulations, the input data groups consists of

1. title card and comments
2. finite difference grid specification, i.e. the number of grid nodes in each direction.
3. lists of grid node coordinates
4. zone definitions that specify the grid locations of distinct strata.
5. rock and hydraulic property specifications
6. convergence and iteration parameters
7. initial pressures and concentrations
8. boundary values and/or fluxes
9. time step and output specifications.

Simulations of multidimensional flow and transport can be performed in either steady state or time-dependent mode.

G.4.2 Output Options

Results from PORFLOW consist of

1. total head
2. saturation
3. moisture content
4. contaminant concentration
5. Darcy velocities

for each grid block in the computational grid. The user can select to print out any or all of the output variables. Each of these variables can be post-processed to produced graphical output.

G.4.3 Documentation of User Instructions

PORFLOW, version 2.4, is documented in Runchal and Sagar (1992). This report describes the mathematical theory and numerical techniques, serves as a user's manual, and provides detailed information on the code organization, selection of computational grids and time steps, input structure, and key-word definitions.

G.5 References

Baca, R. G., R. C. Arnett, P. M. Clifton, and N. W. Kline. 1984. *Repository Horizon Identification Report*, Chapters I-VII, RHO-BW-ST-28P, Rockwell Hanford Operations, Richland, Washington.

Baca, R. G., J. C. Walton, and A. S. Reed. 1988. "Organic Contaminant Release from a Mixed Waste Disposal Site: Analysis of Vapor Transport through the Vadose Zone and Site Remediation." *Proceedings of the Tenth Annual DOE Low-Level Waste Management Conference*, Denver, Colorado.

Bear, J., and Y. Bachmat. 1990. *Introduction to Modelling of Transport Phenomena in Porous Media*. Kluwer Academic Publishers, Boston, Massachusetts.

- Connelly, M. P., J. D. Davis, and P. D. Rittmann. 1991. *Numerical Simulation of ^{90}Sr Transport from the 100-N Area Liquid Waste Disposal Facilities*, WHC-SD-ER-TA-001, Westinghouse Hanford Company, Richland, Washington.
- Eyler, L. L., and M. J. Budden. 1984. *Verification and Benchmarking PORFLO: An Equivalent Porous Continuum Code for Repository Scale Analysis*, PNL-5044, Pacific Northwest Laboratory, Richland, Washington.
- Farmer, C. L. 1984. *A Moving Point Method for Numerical Calculation of Miscible Displacement*, AEEW-R 1895, Winfrith Atomic Energy Establishment, Winfrith, England, UK.
- Freeze, R. A., and J. A. Cherry. 1979. *Groundwater*. Prentice-Hall, Inc., Englewood Cliffs, New Jersey.
- Huyakorn, P. S., and G. F. Pinder. 1983. *Computational Methods in Subsurface Flow*. Academic Press, Inc., New York.
- Kemper, W. O., and J. C. van Schaik. 1966. *Diffusion of Salts in Clay-Water Systems*. Soil Sc. Am. Proc. 30:534-540.
- Kline, N. W., A. K. Runchal, and R. G. Baca. 1983. *PORFLO Computer Code: Users Guide*, RHO-BW-CR-138P, Rockwell Hanford Operations, Richland, Washington.
- Magnuson, S. O., R. G. Baca, and A. J. Sondrup. 1990. *Independent Verification and Benchmark Testing of the PORFLO-3 Computer Code, Version 1.0*, EGG-BG-9175, EG&G Idaho, Inc., Idaho Falls, Idaho.
- Piepho, M. G., and A. K. Runchal. 1991. *A Comparison of Three Methods for Solving Flow Equations of Two Immiscible Fluids in Variably-Saturated Media*, WHC-SA-1289-FP, Westinghouse Hanford Company, Richland, Washington.
- Piepho, M. G., W. H. Sutherland, and P. D. Rittmann. 1993. *The Grout Performance Assessment Code System (GPACS) with Verification and Benchmarking*, WHC-SD-WM-UM-019, Westinghouse Hanford Company, Richland, Washington.
- Piepho, M. G. 1994. *Grout Performance Assessment Results of Benchmark, Base, Sensitivity and Degradation Cases*. WHC-SD-WM-TI-561. Westinghouse Hanford Company, Richland, Washington.
- Rockhold, M. L., and S. K. Wurstner. 1991. *Simulation of Unsaturated Flow and Solute Transport at the Las Cruces Trench Site Using the PORFLO-3 Computer Code*, PNL-7562, Pacific Northwest Laboratories, Richland, Washington.
- Runchal, A. K., B. Sagar, R. G. Baca, and N.W. Kline. 1985. *PORFLO - A Continuum Model for Fluid Flow, Heat Transfer, Mass Transport in Porous Media*, RHO-BW-CR-150P, Rockwell Hanford Operations, Richland, Washington.

Runchal, A. K., and B. Sagar. 1989. *PORFLO-3: A Mathematical Model for Fluid Flow, Heat and Mass Transport in Variably Saturated Geologic Media*. Users' Manual, Ver 1.0, WHC-EP-0042, Westinghouse Hanford Company, Richland, Washington.

Runchal, A. K., and B. Sagar. 1992. *PORFLOW: A Mathematical Model for Fluid Flow, Heat and Mass Transport in Multifluid, Multiphase Fractured or Porous Media*. Users' Manual, Ver 12.4, ACRi/016/Rev G. Analytic and Computational Research Inc., Los Angeles, California.

Sagar, B., and A. K. Runchal. 1990. *PORFLO-3; A Mathematical Model for Fluid Flow, Heat, and Mass Transport in Variably Saturated Geologic Media, Theory and Numerical Methods, Version 1.0*, WHC-EP-0042, Westinghouse Hanford Company, Richland, Washington.

Smoot, J. L., and B. Sagar. 1990. *Three Dimensional Contaminant Plume Dynamics in the Vadose Zone: Simulation of the 241-T-106 Single-Shell Tank Leak at Hanford*, PNL-7221, Pacific Northwest Laboratory, Richland, Washington.

Sonnichsen, J. C. 1991. *Preliminary Performance Assessment Strategy for Single-Shell Tank Waste Disposal*, WHC-EP-0379, Westinghouse Hanford Company, Richland, Washington.

Travis, B. J. 1984. *TRACR3D: A Model of Flow and Transport in Porous/Fractured Media*, LA-9667-MS, Los Alamos National Laboratory, Los Alamos, New Mexico.

U.S. Department of Energy-Richland Operations Office (U.S. DOE/RL). 1982. *Site Characterization Report for the Basalt Waste Isolation Project*, DOE-RL 82-3, U.S. Department of Energy, Richland Operations Office, Richland, Washington.

U.S. DOE/RL. 1991. *Description of Codes and Models to be Used in Risk Assessment*, U.S. Department of Energy, Richland Operations Office, Richland, Washington.

Walton, J. C., and R. R. Seitz. 1991. *Performance of Intact and Partially Degraded Concrete Barriers in Limiting Fluid Flow*, NUREG/CR-5614, U.S. Nuclear Regulatory Commission, Washington, D.C. or EGG-2614, EG&G Idaho, Inc., Idaho Falls, Idaho.

Westinghouse Hanford Company (WHC). 1990. *Liquid Effluent Study Final Project Report*, WHC-EP-0367, Westinghouse Hanford Company, Richland, Washington.

Wittmeyer, G. W., and B. Sagar. 1992a. INTRAVAL Project: Las Cruces Trench Solute Transport Modeling Study, Plot 2, Experiments A and B. Report for Research Activities for Calendar Year 1991. W. C. Patrick, ed. CNWRA 91-01A. San Antonio, Texas.

Wittmeyer, G. W., and B. Sagar. 1992b. INTRAVAL Project: Las Cruces Trench Unsaturated Flow Modeling Study, Plot 2, Experiment B. NRC High-Level Radioactive Waste Research at CNWRA for Calendar January 1 through June 30, 1992. W. C. Patrick, ed. CNWRA 92-015. San Antonio, Texas.

Appendix H

Verification and Benchmark Testing of the Flow and Transport Codes Used for the Hanford Grout Performance Assessment

Appendix H

Verification and Benchmark Testing of the Flow and Transport Codes Used for the Hanford Grout Performance Assessment

**M. L. Rockhold, Pacific Northwest Laboratory
W. H. Sutherland, Westinghouse Hanford Company
C. A. Oster and D. W. Langford, Boeing Computer Services**

H.1 Introduction

Computer codes were used to model unsaturated flow and contaminant transport for the performance assessment of grouted double-shell tank waste disposal at the Hanford Site. These computer codes were tested and evaluated to verify their capability of correctly simulating the type of problems related to the performance assessment. These computer codes include PORFLOW (Runchal and Sagar 1992), S301 (Wikramaratna and Farmer 1987), and TRACR3D (Travis and Birdsell 1991). This appendix describes the results of selected verification and benchmark test problems that were simulated with these codes.

Numerous methods exist for testing computer codes. These methods include 1) mass balance and consistency checks within a computer code during execution, 2) crosschecks between sequential runs of the same problem using finer spatial and temporal discretizations, 3) comparisons of numerical solutions with selected analytical solutions (a.k.a. verification), and 4) comparisons of numerical solutions from one code with solutions from another code for the same problem (a.k.a. benchmarking).

Computer codes can also be tested by comparing simulation results with observations from actual laboratory or field experiments. These comparisons test the conceptual model of the specific field site or experiment, the physics or mathematical representation of it, and the adequacy of the site or experimental characterization data. No single test method is sufficient to confirm that a computer code correctly calculates results. However, when used together the methods provide confidence that a code can reliably calculate correct results for the types of situations and conditions modeled.

The primary emphasis of this appendix is on the verification and benchmark testing of the PORFLOW, TRACR3D, and S301 computer codes. Additional verification and benchmark testing of the version of PORFLOW that was used for the performance assessment is described by Piepho et al. (1993). The results from independent verification and benchmark testing of an earlier version of the PORFLOW

code were reported by Magnusen, Baca, and Sondrup (1990). Benchmark comparisons between the PORFLOW and TRACR3D codes were also reported by Magnusen, Baca, and Sondrup (1990) and Thomas (1991).

This appendix is organized as follows. Governing equations used for unsaturated flow and contaminant transport modeling are discussed in Section H.2. Brief descriptions of the PORFLOW, TRACR3D, and S301 codes are presented in Section H.3. The performance indicators used to evaluate simulation results are described in Section H.4. Section H.5 contains a description of the verification and benchmark test problems and the results. The conclusions are given in Section H.6, and cited references are listed in Section H.7.

H.2 Governing Equations

Natural and engineered components of the proposed grout waste isolation system at the Hanford Site compose a geochemically complex, three-dimensional, multiphase, nonisothermal system. Here, the term multiphase refers to multiple fluid phases (i.e., aqueous and gas phases). This system was modeled as a two-dimensional, isothermal, single-phase (aqueous) system primarily for computational efficiency. The simplification to a two-dimensional system was justified because of the length-to-height ratio of the unsaturated zone and because of plans to construct the grout vaults in pairs. In addition, water flow in the unsaturated zone is predominantly vertical and moves into a horizontal, saturated flow system whose water table is essentially unaffected by the overlying grout facility. Nonisothermal effects associated with grout curing, asphalt cooling, and heat generation by the waste were assumed to be relatively insignificant.

The flow of a single fluid phase (water) and the transport of water-soluble contaminants under isothermal conditions are described using two governing mass conservation equations. The isothermal flow of water in a rigid, variably saturated porous medium is described using the Richards equation (Richards 1931). The two-dimensional form of the Richards equation is written as follows:

$$\frac{\partial \theta}{\partial t} = \frac{\partial}{\partial x} \left[K_{xx} k_r \frac{\partial h}{\partial x} \right] + \frac{\partial}{\partial z} \left[K_{zz} k_r \left(\frac{\partial h}{\partial z} + 1 \right) \right] \quad (1)$$

where θ = volumetric water content (L^3/L^3)

t = time

K_{xx} = horizontal component of saturated hydraulic conductivity tensor (L/T)

K_{zz} = vertical component of saturated hydraulic conductivity tensor (L/T)

k_r = relative permeability (dimensionless)

h = pressure head (L)

x = horizontal coordinate (L)

z = vertical coordinate (L).

The primary dependent variable in Equation 1 is pressure head, h . Pressure head is linked to the secondary variables, θ , K , and k_r , by constitutive relations representative of the physical and hydraulic properties of the fluid and porous medium. Note that the principal directions of anisotropy are aligned with the cartesian coordinate system so that the cross-components of the saturated hydraulic conductivity tensor are 0.

The van Genuchten (1980) model, given by Equations (2) and (3), was used to describe the constitutive relations for relative permeability (k_r), effective saturation (S_e), and pressure head (h).

$$\theta = \begin{cases} \theta_s & h \geq 0 \\ \theta_r + (\theta_s - \theta_r)[1 + (-\alpha h)^n]^{-m} & h < 0 \end{cases} \quad (2)$$

$$k_r = S_e^{1/2} \left[1 - \left(1 - S_e^{1/m} \right)^m \right]^2 \quad (3)$$

where θ_s = saturated water content (L^3/L^3)

θ_r = residual water content (L^3/L^3)

α, n = curve-fitting parameters (L^{-1} , dimensionless)

$m = 1 - 1/n$

$S_e = (\theta - \theta_r)/(\theta_s - \theta_r)$.

Transport of a conservative solute is described by the convective-dispersive mass transport equation, which is written as:

$$\begin{aligned} & \frac{\partial}{\partial x} \left(D_{xx} \frac{\partial c}{\partial x} \right) + \frac{\partial}{\partial z} \left(D_{zz} \frac{\partial c}{\partial z} \right) + \frac{\partial}{\partial x} \left(D_{xz} \frac{\partial c}{\partial z} \right) \\ & + \frac{\partial}{\partial z} \left(D_{zx} \frac{\partial c}{\partial x} \right) - V_x \frac{\partial c}{\partial x} - V_z \frac{\partial c}{\partial z} - \lambda c = \frac{\partial c}{\partial t} \end{aligned} \quad (4)$$

where $D_{xx}, D_{zz}, D_{xz}, D_{zx}$ = dispersion coefficients (L/T^2)

c = solute concentration (M/L^3)

V_x, V_z = x- and z-components of Darcy velocity vector (L/T)

λ = solute or species reaction rate (T^{-1}).

The dispersion coefficients incorporate the effects of hydrodynamic mixing and molecular diffusion. The common assumption that hydrodynamic dispersion is linearly proportional to the average pore water velocity (Bear 1972) leads to the following expressions for the dispersion coefficients (Scheidegger 1961):

$$D_{xx} = \alpha_L \frac{V_x^2}{|V|} + \alpha_T \frac{V_z^2}{|V|} + D_m \quad (5)$$

$$D_{zz} = \alpha_T \frac{V_x^2}{|V|} + \alpha_L \frac{V_z^2}{|V|} + D_m \quad (6)$$

$$D_{zx} = D_{xz} = (\alpha_L - \alpha_T) \frac{V_x V_z}{|V|} \quad (7)$$

where α_L, α_T = longitudinal and transverse dispersivities (L)

D_m = bulk solution coefficient of molecular diffusion (L^2/T).

A modified form of the dispersion coefficient used in the performance assessment simulations will be described later in this appendix for the second set of benchmark problems.

H.3 Code Descriptions

The PORFLOW, TRACR3D, and S301 codes are briefly described in this section. Complete descriptions of the numerical methods implemented in the different codes are given in the respective users' manuals or in theory documents cited below.

H.3.1 PORFLOW

PORFLOW Version 2.394gr was the primary numerical model used to support the performance assessment calculations. PORFLOW is a proprietary code that is copyrighted by Analytical and Computational Research, Inc., subject to limited government license (Runchal and Sagar 1992). Version 2.394gr is a fully three-dimensional, Eulerian (or fixed grid) finite difference code designed to simulate multiphase fluid flow, heat transfer, and multicomponent mass transport in variably saturated, heterogeneous, and anisotropic porous media.

The governing mass conservation equations and constitutive relations that were used by PORFLOW for the performance assessment simulations are essentially those shown in Equations (1-5). The governing equations were solved using an integrated finite difference method (Patankar 1980). Time derivatives were approximated using a first-order, implicit (backward difference) scheme. Several direct and iterative solution options were available to solve the resulting nonlinear algebraic equations. An alternating-direction-implicit scheme with Picard iteration (Huyakorn and Pinder 1983) was also used for the performance assessment simulations.

H.3.2 TRACR3D

The TRACR3D code is also a fully three-dimensional, Eulerian finite difference code that is designed to simulate multiphase fluid flow and multicomponent mass transport in variably saturated, heterogeneous, and anisotropic porous media (Travis and Birdsell 1991). TRACR3D does not account for heat transfer and, therefore, will only solve isothermal flow and transport problems. TRACR3D was used to model water flow for the benchmark and verification problems in this appendix. The code's solute transport simulation capabilities were not formally tested. The TRACR3D code is in the public domain and available from Los Alamos National Laboratory.

Like PORFLOW, TRACR3D also uses an integrated finite difference method. However, the resulting nonlinear finite difference equations are linearized and solved using an iterative Newton-Raphson technique (Huyakorn and Pinder 1983). Newton-Raphson implementations typically require more memory and more computational effort per iteration than Picard implementations, but they are quadratically convergent as opposed to linear. As a result, the Newton-Raphson method allows larger time steps and is more robust than the Picard method for highly nonlinear problems.

The PORFLOW and TRACR3D codes use cell-centered and node-centered finite difference schemes, respectively. In the cell-centered scheme, the node positions are specified, and the cell faces are

placed at the midpoints between nodes. In the node-centered finite difference scheme, the positions of the cell faces are specified, and the nodes are placed at the midpoints between the cell faces. The two schemes are identical for uniform grids, but can result in different node locations for nonuniform grids.

H.3.3 S301

The version of the S301 code used for these simulations is a two-dimensional, mixed Eulerian-Lagrangian code originally designed to simulate solute transport under steady, saturated flow conditions (Wikramaratna and Farmer 1987). The code was modified to use saturation and velocity fields generated by TRACR3D to perform transient transport simulations under unsaturated conditions. The S301 code was obtained through the purchase of a use agreement from the United Kingdom Atomic Energy Authority.

S301 code uses an explicit, 9-point finite difference approximation to generate solutions with minimal grid orientation effects (Wikramaratna and Farmer 1987). S301 uses the modified method of characteristics (Chiang, Wheeler, and Bedient 1989) to develop a first approximation of concentrations at new time levels. An adaptive moving point (particle tracking) technique is then used as an error recovery procedure in regions where numerical dispersion is significant (Farmer 1985). These regions are determined by calculating where grid Peclet numbers and concentration gradients exceed given threshold values (Wikramaratna and Farmer 1987). The S301 code was used to model solute transport for the verification and benchmark problems in this appendix.

H.4 Performance Indicators

Various performance indicators can be used to evaluate the accuracy of results generated by numerical models. Performance indicators should be selected to match the purpose of the simulations. For example, if a numerical model is used to forecast contaminant movement in groundwater, then the travel time of the contaminant from the source to some point of compliance, such as a water supply well, is a good performance indicator. Calculated fluxes crossing specified horizontal or vertical planes as a function of time, and contaminant arrival curves are also useful for evaluating the performance of numerical flow and transport codes for this type of application.

Other quantitative indicators of model performance include maximum absolute deviation, root-mean-squared error, and relative-root-mean-squared error. These are general indicators, but they can be useful for relative comparisons between the results generated by numerical models and analytical solutions.

Several performance indicators were used to evaluate the numerical models for this verification and benchmarking effort. For the verification problems, relative-root-mean-squared (RRMS) error calculations were used to provide a quantitative basis for comparing numerical and analytical solutions. The RRMS error was defined as:

$$RRMS = \sqrt{\sum_{i=1}^k \frac{[(a_i - n_i)/a_i]^2}{k}} \quad (8)$$

where a_i = analytical solution at point i

n_i = numerical solution at point i

k = number of comparison points.

Magnusen, Baca, and Sondrup (1990), who also used the RRMS error as a performance indicator, judged the accuracy of verification test results by defining four performance categories. These categories were 1) Excellent - $RRMS \leq 0.01$, 2) Good - $RRMS \leq 0.05$, 3) Acceptable - $RRMS \leq 0.10$, and 4) Unacceptable - $RRMS > 0.10$. The ranges for these categories were arbitrarily selected and, thus, are meaningless with respect to quantifying contaminant fluxes or arrival times. Therefore, in this appendix, RRMS values are only used to provide a quantitative basis for relative comparisons.

For the benchmark problems, instantaneous fluxes crossing specified vertical and horizontal planes, and outflow arrival distribution curves were used to compare the results generated by the different numerical models. Contour plots of water content or normalized concentrations were also generated for qualitative comparisons.

H.5 Descriptions of Test Problems and Simulation Results

Two verification problems were selected to test the PORFLOW, TRACR3D, and S301 codes. The first verification problem tested the ability of the PORFLOW and TRACR3D codes to simulate two-dimensional water infiltration into homogeneous, unsaturated soil. The second verification problem tested the ability of the PORFLOW and S301 codes to simulate two-dimensional solute transport in a homogeneous medium, with different grid Peclet numbers. These verification problems also constituted benchmarks for the respective codes. Two additional sets of benchmark simulations were conducted to compare the results generated by the different codes for more realistic flow and transport problems similar to the type required for the performance assessment.

H.5.1 Verification Test Problem 1

The first verification test problem was designed to test the ability of the PORFLOW and TRACR3D codes to simulate the advance of a moisture front into homogeneous soil from a surface infiltration source. The analytical and numerical solution problem domains, and the boundary and initial conditions for this problem are illustrated in Figure H.1. The analytical solution problem domain is the semi-infinite plane below the $z = 0$ line shown in Figure H.1. The boundary conditions along the top of the domain are Neumann, with the flux = 0 for $x < -5$ cm and $x > 5$ cm, and an infiltration flux (expressed as a rate per unit width and length) for the strip source of $400 \text{ cm}^3/\text{cm}^2/\text{d}$. No boundary conditions were imposed along the other boundaries for the analytical solution problem domain, because they extend to infinity.

Warrick and Lomen (1976) developed an analytical solution for this problem using a Kirchoff integral transformation (Carslaw and Jaeger 1959) and defining a matric flux potential, ϕ , after Gardner (1958) as:

$$\phi = \int_{h_{\min}}^h K(h) dh \quad (9)$$

with

$$K(h) = K_0 \exp(\alpha h) \quad (10)$$

where $h_{\min}$ = initial pressure head (L)

h = pressure head (L)

K = hydraulic conductivity (L/T)

K_0 = saturated hydraulic conductivity (L/T)

α = empirical constant (L^{-1}).

The pressure head, h , is then equal to:

Figure H.1. Analytical and Numerical Solution Problem Domains and Boundary and Initial Conditions for Verification Test Problem 1

$$h(x,z,t) = 1/\alpha \ln(\alpha/K_0 \phi) \quad (11)$$

where

$$\phi(X,Z,T) = (q_0/2\pi) \Phi(X,Z,T) \quad (12)$$

and

$$\begin{aligned} \Phi(X,Z,T) = & \frac{\sqrt{\pi} \exp Z}{2X_0} \int_0^T \left[\tau^{-1/2} \exp(-\tau - Z^2/4\tau) \right. \\ & - \sqrt{\pi} \exp Z \operatorname{erfc}(Z/2 \sqrt{\tau} + \sqrt{\tau}) \Big] \\ & \cdot \left[\operatorname{erf} \left\{ (X + X_0)/2 \sqrt{\tau} \right\} - \operatorname{erf} \left\{ (X - X_0) / 2\sqrt{\tau} \right\} \right] d\tau \end{aligned} \quad (13)$$

The dimensionless variables $X = \alpha x/2$, $Z = \alpha z/2$, and $T = \alpha kt/4$ were introduced to facilitate obtaining the analytical solution. The parameters x and z are the true (unscaled) horizontal and vertical distances, respectively, measured from the center of the surface strip source, and t is the actual (unscaled) time. The terms erf and erfc are the standard definitions of the error function and the complementary error function, respectively (Abramowitz and Stegun 1964). The integral in Equation (13) was evaluated numerically using the IMSL subroutine DQDAGS (IMSL 1987).

Celia, Ahuja, and Pinder (1987) and Bouloutas (1989) compared numerical solutions with the analytical solution by Warrick and Lomen (1976) for infiltration from a surface strip source using parameters reported by Warrick (1974) for the Panoche loam soil. Volumetric water content was expressed as a function of pressure head as:

$$\theta(h) = (K_0/A) \exp(\alpha h) \quad (14)$$

with the values of K_0 , α , and A taken to be 100 cm/d (0.0694 cm/min), 0.04 m^{-1} , and 200 cm/d (0.1388 cm/min), respectively. The half-width of the strip source was taken to be 5 cm. The surface boundary flux, q , was set equal to 400 cm²/d (0.277 cm²/min), and the initial pressure head was set equal to -250 cm. Warrick and Lomen (1976) used a value of $h_{\min} = -\infty$ as initial and boundary conditions, but their solution is applicable for other initial and boundary conditions, provided that the boundaries are

located a sufficient distance from the source. For the numerical simulations of this problem, the bottom and right-hand side boundaries were maintained at an initial pressure head of -250 cm.

The problem described above was simulated using the PORFLOW and TRACR3D codes. A non-uniform grid with 29 nodes in the x-direction and 31 nodes in the z-direction was used to discretize the 80-cm-wide by 100-cm-deep model domain. The numerical solution problem domain and boundary and initial conditions are also shown in Figure H.1. The numerical model domain represents the right-hand side of the analytical solution problem domain, assuming an axis of symmetry along the center line of the surface strip source.

For the computational grid used by TRACR3D, the coordinates of the nodes in the x-direction are 0.5, 1.5, 2.5, 3.5, 4.5, 5.5, 6.75, 8.5, 10.5, 12.5, 14.5, 16.5, 18.5, 20.5, 22.5, 24.5, 26.5, 28.5, 31.0, 34.5, 38.5, 42.5, 46.5, 50.5, 54.5, 58.5, 63.0, 69.0, and 76.25 cm. The z-coordinates of the nodes used by TRACR3D are 0.5, 1.5, 2.5, 3.5, 4.5, 5.5, 6.75, 8.5, 10.5, 12.5, 14.5, 16.5, 18.5, 20.5, 22.5, 24.5, 26.5, 28.5, 31.0, 34.5, 38.5, 42.5, 46.5, 50.5, 54.5, 58.5, 63.5, 70.5, 78.5, 86.5, and 95.25 cm. The analytical solution was evaluated at these same node coordinates.

The x-coordinates of the nodes used for PORFLOW simulations were the same as those used for the TRACR3D simulations, except for nodes at 6.5, 30.5, 62.5, 68.5, and 76.5 cm. Similarly, the z-coordinates of the nodes used for PORFLOW simulations differed from TRACR3D by nodes at 6.5, 30.5, 62.5, and 94.5 cm. The above listed node coordinates were used in the PORFLOW simulations in place of the closest respective node coordinates listed for TRACR3D. As noted previously, the differences in the node locations were a result of the node-centered versus cell-centered finite difference schemes used by TRACR3D and PORFLOW, respectively.

The numerical solutions for this verification test problem are shown with the analytical solution results for time equal to 72 minutes in Figure H.2. The RRMS errors for the PORFLOW and TRACR3D solutions are 0.042 and 0.011, respectively. The RRMS error calculations were only made at node coordinates that were common to both the analytical and numerical solution grids. In addition, comparisons were only made for values of pressure head ≥ -200 cm.

The numerical solutions from both TRACR3D and PORFLOW appeared to match the analytical solution relatively well. No grid convergence tests were conducted for this problem, but the RRMS errors would presumably be even smaller if finer spatial discretizations were used for the numerical model grids.

H.5.2 Verification Test Problem 2

The second verification test problem was designed to test the ability of the PORFLOW and S301 codes to simulate two-dimensional solute transport in a saturated, homogeneous porous medium. Numerical solutions were obtained using PORFLOW and S301 with different grid Peclet numbers to test the accuracy and stability of the different transport schemes.

Figure H.2. Pressure Head at $t = 72$ Minutes for Verification Test Problem 1

For a one-dimensional system, the grid Peclet number, Pe , is defined as:

$$Pe = V \, dx/D \quad (15)$$

where V = Darcy velocity (L/T)

dx = grid block size (L)

D = dispersion coefficient (L^2/T).

The grid Peclet number is a measure of the relative strengths of diffusion and advection, with a Peclet number of 0 corresponding to a pure diffusion problem. The grid Peclet number can be used along with the Courant number to identify potential inaccuracies in numerical solutions to the transport equation. The Courant number, Cn , is defined as:

$$Cn = V \, dt/dx \quad (16)$$

where dt is the time step size, and all other symbols have been previously defined. "Rules-of-thumb," that $Pe \leq 2$, and $Cn \leq 1$, are frequently followed to ensure the accuracy and stability of numerical solutions to the convective-dispersive mass transport equation for many standard finite difference approximations. Maintaining Cn at a value ≤ 1 prevents solute particles from traveling more than one grid block per time step.

The spatial and temporal discretizations required to satisfy the Pe and Cn conditions are not always practical for large problem domains. If the grid Peclet or Courant numbers violate the above criteria, then the process of differencing the advective terms in the transport equation may introduce a diffusive error effect, which behaves as though the fluid possesses an artificial diffusivity of magnitude ϵ_a (Trent 1975). This diffusive error effect can result in shorter-than-actual arrival times and lower predicted peak concentrations. The magnitude of this error (a.k.a. numerical dispersion) can be approximated by:

Upwind: $\epsilon_a = 1/2 \, V \, dx \, (1-Cn) \quad (17)$

Central-Space: $\epsilon_a = 1/2 \, V^2 \, dt \quad (18)$

for upwind weighting and central-space differencing schemes (Trent 1975). Note that for the upwind differencing scheme, the diffusive error effect goes to 0 for $Cn = 1$. However, this situation is realistically obtainable only for one-dimensional flow (Trent 1975). Failure to satisfy the Pe number criteria also results in a diffusive error effect.

Note, also, that upwind differencing suffers from considerably more numerical dispersion for small values of the Courant number, which suggests it should be replaced by central-space differencing for small values of Cn (Trent 1975). However, the central-space differencing scheme may become unstable if the grid Pe number exceeds a critical value of 2 (Patankar 1980). The PORFLOW code uses a hybrid scheme to combat this difficulty. This scheme uses central-space differencing when the local grid Pe number is <2 , and upwind weighting when the Pe number >2 (Runchal and Sagar 1992). However, no checks are made within PORFLOW to ensure that the Courant condition is satisfied. Therefore, it is the user's responsibility to ensure this condition is satisfied.

The effective artificial dispersivity, α_a , that can be generated by standard finite difference approximations to the convective-dispersive mass transport equation can be calculated by:

$$\alpha_a = \epsilon_a / V \quad (19)$$

The analytical solution domain that was selected to test the transport algorithms consists of a two-dimensional area with a line source of finite length at the inlet boundary. The edges of the inlet boundary were assumed to be an infinite distance away from the line source. The outlet boundary was assumed to be located an infinite distance from, and perpendicular to the inlet boundary. The analytical and numerical solution model domains for this problem are depicted in Figure H.3.

Figure H.3. Analytical and Numerical Solution Problem Domains and Boundary and Initial Conditions for Verification Test Problem 2

The analytical solution is given by Cleary and Ungs (1978) in Equation 20,

$$C(X,Y,t) = \frac{C_o X}{4\sqrt{\pi D_x}} \exp \left\{ \frac{V_x X}{2D_x} - \gamma t \right\} \cdot \int_{\tau=0}^t \frac{\exp \left\{ - \left(K - \gamma + \frac{V_x^2}{4D_x} \right) \tau - \frac{X^2}{4D_x \tau} \right\}}{\tau^{3/2}} \cdot \left[- \operatorname{erfc} \left\{ \frac{(Y_2 - Y)}{2\sqrt{D_y \tau}} + \frac{V_y}{2} \sqrt{\frac{\tau}{D_y}} \right\} + \operatorname{erfc} \left\{ \frac{(Y_1 - Y)}{2\sqrt{D_y \tau}} + \frac{V_y}{2} \sqrt{\frac{\tau}{D_y}} \right\} \right] d\tau \quad (20)$$

where all symbols have been defined previously. The integral in Equation 20 was evaluated numerically using the IMSL subroutine DQDAGS (IMSL 1987).

The transport verification problem described above was simulated for several grid Peclet numbers to test the accuracy and stability of the numerical schemes used by the PORFLOW and S301 codes. A 1-m-long by 0.5-m-wide model domain was discretized using uniform 0.025-m node spacing in both the x- and y-directions. This discretization resulted in 40 nodes in the x-direction and 20 nodes in the y-direction, totaling 800 nodes in the active computational domains. A line source was specified along the left boundary of the model domains, extending from $y = 0$ m to $y = 0.25$ m. A dimensionless concentration of 1.0 was specified for the source strength. A constant Darcy velocity of 10 m/d was specified for the longitudinal or x-direction, with a constant Darcy velocity of 0 m/d in the transverse or y-direction. The numerical model domain and boundary and initial conditions for this problem are shown in Figure H.3.

The computational grids and velocities were held constant for all simulation cases. The time steps were allowed to vary from a minimum of $1.25E-3$ days to a maximum of approximately $2.5E-3$ to satisfy the Cn condition. The S301 code automatically checked the Cn condition and adjusted the time steps as needed to satisfy the condition $Cn \leq 1$.

The diffusion coefficients were varied to generate grid Peclet numbers of 2.222, 80, and 2222. The grid Peclet number 2.222 resulted in a diffusion dominated transport problem. The grid Peclet numbers 80 and 2222 resulted in advection dominated problems. Figure H.4 shows the results from the analytical solution and the numerical solutions obtained using PORFLOW and S301, for $t = 0.08$ days, with a grid Peclet number of 2.222. The relative concentration contours for all three solutions are quite similar.

The results from the analytical and numerical solutions for Peclet numbers 80 and 2222 are shown in Figures H.5 and H.6, respectively. The numerical solutions for the high Peclet number cases are not as close to the analytical solution as the results for the diffusion dominated case. However, the results obtained using the particle tracking feature in S301 (S301-P) are much closer to the analytical solution than the results obtained using the fully Eulerian methods.

The RRMS errors that were calculated for the PORFLOW and S301 solutions for the 3 Peclet numbers are shown in Table H.1 for time = 0.08 days. No boundary nodes, and only concentrations ≥ 0.001 and ≤ 0.999 were used in the RRMS calculations. A lower limit was imposed on the concentrations used in the RRMS calculations to avoid comparing very small numbers, which can result in large RRMS errors. RRMS error values computed for other times were similar to the values for $t = 0.08$ days, with no obvious increases or decreases as a function of time.

The contour plots of relative concentration for this problem indicate the numerical solutions matched the analytical solution fairly well for the case with a grid Peclet number of 2.222. However, the other cases with larger grid Peclet numbers demonstrate the effects of excessive numerical dispersion.

The S301 code required approximately 7 times more computational effort (CPU time) for this 800-node verification problem when the particle tracking option was invoked (S301-P), relative to the solution obtained using only the modified method of characteristics without particle tracking (S301). The run times required for the PORFLOW and S301 solutions, without particle tracking, were comparable. As shown by the RRMS values and contour plots, the solutions obtained using the particle tracking feature in S301 were more accurate. However, the particle tracking feature was found to be much more computationally expensive and impractical to use for the larger performance assessment simulations.

The inability to control numerical dispersion is inherent in many numerical transport codes. In theory, the grid Peclet and Courant numbers can be reduced to eliminate or reduce inaccuracies in solutions of the transport equation by decreasing the node spacing and reducing the size of the time steps. However, in practice, grid refinements and time steps that are small enough to eliminate numerical dispersion using standard finite difference or finite element solution methods often result in excessive simulation time that is impractical for simulating large-scale, transient unsaturated flow and transport problems. The excessive CPU time needed by the S301 code with particle tracking for problems the size of those required for the performance assessment was the primary motivation for using the PORFLOW code instead of TRACR3D and S301.

Although contaminant arrival curves and mass fluxes as a function of time were not compared for these verification problems, such comparisons were made previously by Magnusen, Baca, and Sondrup (1990). These comparisons showed good agreement between the results generated by PORFLOW and analytical or quasi-analytical solutions for two- and three-dimensional flow and transport problems.

H.5.3 Issues Regarding Internodal Conductance Averaging

In general, the results generated by PORFLOW and TRACR3D have compared favorably with each other and with analytical solutions for simple two-dimensional, unsaturated flow and transport problems with homogeneous porous media when the grid Peclet and Courant conditions were satisfied. However, the results generated by PORFLOW and TRACR3D have been quite different when the simulated problems involved heterogeneous media with highly contrasting material properties (Magnusen, Baca, and Sondrup 1990; Thomas 1991). These differences have been attributed primarily to the different methods used to calculate internodal hydraulic conductivities and velocity components.

TRACR3D computes internodal conductances using the product of the harmonic mean values of intrinsic permeabilities and upwind (or upstream) weighted relative permeabilities. PORFLOW computes internodal conductances using simple arithmetic, geometric, or harmonic averaging of the hydraulic conductivities in adjacent grid blocks.

Under fully water-saturated conditions, the harmonic mean is physically correct and is typically used for saturated flow modeling. However, for unsaturated conditions, hydraulic conductivity is a non-linear function of capillary pressure or water content, and there is no consensus regarding a general finite difference internodal conductivity averaging scheme that is practical and accurate under all conditions.

Table H.1. RRMS Values for Verification Problem 2

Peclet Number	RRMS ^(a)		
	PORFLOW	S301	S301-P
2.222	0.2750	0.1779	0.1897
80.0	10.6131	19.4604	1.4913
2222.0	111.2601	186.4761	0.8389

(a) RRMS values calculated for $0.001 \leq C/C_0 \leq 0.999$.

Figure H.4. Relative Concentrations at $t = 0.08$ Hours for Verification Test Problem 2 with Grid Peclet Number = 2.222

Figure H.5. Relative Concentrations at $t = 0.08$ Hours for Verification Test Problem 2 with Grid Peclet Number = 80.0

Figure H.6. Relative Concentrations at $t = 0.08$ Hours for Verification Test Problem 2 with Grid Peclet Number = 2222.22

Numerous researchers have investigated the effects of various internodal conductance averaging schemes. Brutsaert (1971) suggested that full upstream weighting of hydraulic conductivities is the most appropriate averaging scheme for problems in which saturations vary rapidly with time (e.g., infiltration fronts, cone of depression near a well bore). Haverkamp and Vauclin (1979) found the geometric mean to be the most preferable weighting option in terms of flexibility, accuracy, and feasibility for simulating one-dimensional transient water flow in partially saturated soil. Schnabel and Ritchie (1984) conducted one-dimensional simulations of infiltration in partially saturated soil and suggested that when possible the hydraulic conductivity-capillary pressure function should be integrated to determine internodal conductances. The geometric mean was suggested as a second choice for the soils in their study. The harmonic mean was found to yield unrealistic results for all unsaturated flow simulations, particularly when simulating infiltration into soils with very dry initial conditions.

Schnabel and Ritchie (1984) determined that the time required to attain steady-state decreased in order from harmonic to geometric to arithmetic to upstream weighted conductance, while the calculated flux increased in the same order, from the harmonic through the upstream weighted conductance. Thus, the rate at which a simulated front moves or a pulse dissipates should occur in the inverse order, with the rate being greatest for the upstream weighted and least for the harmonic mean conductance.

Zaidel and Russo (1992) and Warrick (1991) showed that an averaging scheme based on the Kirchhoff integral transformation (as described previously for verification test problem 1) is the most accurate internodal hydraulic conductivity averaging scheme for homogeneous media. This transformation is based on the integration of the hydraulic conductivity-capillary pressure function and linearizes the capillary component of the Darcy velocity giving an exact value of fluid flux between grid blocks. However, when the constitutive relations between capillary pressure, saturation, and relative permeability are spatially dependent (i.e., in heterogeneous porous media systems) or are not analytically integrable, the use of the Kirchhoff transformation in a numerical procedure requires excessive computational effort (Zaidel and Russo 1992). Therefore, the procedure is generally not considered to be practical.

Zaidel and Russo (1992) stated that "... we may conclude that there is no universal weighting scheme capable of following successfully sharp fronts for a relatively coarse grid. Of course, the errors introduced by all the weighting schemes diminish if Δx is reduced, but this may require a huge computational effort, especially when simulation of multidimensional flow in relatively large domains is concerned." Zaidel and Russo (1992) suggested that local adaptive grid refinement techniques may be effective in reducing the errors associated with internodal hydraulic conductivity averaging for unsaturated flow modeling.

Judging from these references, the original permeability averaging scheme employed in the TRACR3D code appears to be well suited for simulating problems with sharp fronts in which saturations vary rapidly with time. The scheme used in TRACR3D also reduces to simple harmonic averaging when the porous medium is fully water saturated, which is physically correct under such conditions. This scheme also facilitates the numerical implementation of zero-flux default boundary conditions. However,

as will be shown, the original internodal conductance averaging scheme that is used in TRACR3D can generate results quite different from those generated using simple arithmetic or harmonic averaging.

Modifications to TRACR3D were necessary to obtain results comparable with PORFLOW for simulations with heterogeneous porous media. Options were added for using harmonic, geometric, arithmetic, and weighted conductance averaging schemes. PORFLOW was not modified.

H.5.4 Benchmark Test Problem 1

A small-scale benchmark problem was developed based on literature pertaining to the effects of various internodal conductance averaging schemes. The problem was designed to test whether the averaging options added to TRACR3D were implemented correctly and to determine if the different internodal conductance averaging schemes were the primary cause for the differences observed in larger scale benchmark simulation results from TRACR3D and PORFLOW. Benchmark problem 1 simulated two-dimensional water flow in a vertical cross section consisting of a sloping clay layer embedded within coarse sandy material. This problem was analogous to water flow through and around the clay cap that is part of the final cover required by the Resource and Conservation Recovery Act (RCRA) for hazardous waste landfills in Title 40 of the *Code of Federal Regulations* (40 CFR).

A schematic of the modeled two-dimensional cross section for benchmark problem 1 is shown in Figure H.7. The modeled domain represented a 36-m-wide by 6-m-deep cross section, with uniform 0.4-m node spacing in the horizontal direction and uniform 0.3-m node spacing in the vertical direction. This spatial discretization resulted in 90 nodes in the horizontal direction and 20 nodes in the vertical direction, for a total of 1800 nodes in the active computational domain.

A sloping, 28-m-wide by 0.6-m-thick clay cap was embedded within the modeled domain. Because of constraints imposed by the cartesian grid system, the 7.5% slope of the clay cap was represented using a series of 7 "stair steps" extending downward from the left edge of the modeled domain. This problem was similar in dimension to the upper part of the modeled domain used for the performance assessment simulations. The thickness of the clay cap was represented by 2 nodes for this benchmark problem.

The U.S. Environmental Protection Agency's (EPA) technical guidance document for final covers on hazardous waste landfills and surface impoundments (EPA/530-SW-89-047) requires a minimum thickness of 0.6 m for the low-permeability layer in the final cover (i.e., the clay cap), with a slope $\geq 3\%$. The slope and thickness of the clay cap were approximately 10% and 0.6 m, respectively, as discretized in the base case for the revised performance assessment. A minimum of 3 nodes was used to represent the thickness of the clay cap in the finite difference grid for the performance assessment simulations.

Two internal flux planes were specified for benchmark problem 1. The instantaneous and cumulative fluxes crossing these planes were calculated as a function of time. To quantify the flux of water passing through the clay cap, a horizontal flux plane was specified, extending from the left edge of the model domain to the right edge of the clay cap at a depth of 3.6 m below the surface. To quantify the flux of

Figure H.7. Schematic View of Modeled Two-Dimensional Cross Section and Boundary Conditions for Benchmark Problem 1

water diverted laterally around the clay cap, a vertical flux plane was specified, extending from the surface to a depth of 3.6 m at the right edge of the clay cap. These flux planes are also depicted in Figure H.7.

A uniform flux, corresponding to a recharge rate of 0.1 cm/yr, was specified for the upper boundary condition of the model domain. The lower boundary was held at a pressure head of approximately -481.5 cm, which corresponded to a volumetric water content of 0.04058 for the backfill soil. This water content and pressure head were consistent with a 0.1 cm/yr recharge rate and a unit hydraulic gradient. A unit hydraulic gradient boundary condition would have been more appropriate for this problem, but this option was not available in the PORFLOW code. Lateral boundaries were specified as zero-flux or no-flow boundaries. The initial conditions were specified as uniform liquid saturations of 0.265958 and 0.9241 for the backfill soil and clay cap, respectively. The water retention and saturated hydraulic conductivity parameters that represented the backfill soil and clay cap for this benchmark problem are listed in Table H.2.

Benchmark problem 1 was simulated with PORFLOW by using arithmetic and harmonic averaging of the intermodal hydraulic conductivities for a 500-year simulation period. This problem was also simulated with TRACR3D by using arithmetic, geometric, and harmonic averaging, in addition to the code's original averaging scheme, which uses the product of the harmonic mean of intrinsic permeabilities and fully upstream weighted relative permeabilities.

Table H.2. Water Retention and Hydraulic Conductivity Parameters for Benchmark Problem 1

Material Type	Ks(cm/s)	θ_s	θ_r	$\alpha(\text{cm}^{-1})$	n
Backfill Soil	3.0×10^{-2}	0.376	0.018	0.086	1.742
RCRA Clay Cap	9.4×10^{-9}	0.448	0.000	5.4×10^{-4}	1.324

In Figure H.8, instantaneous fluxes passing through the horizontal and vertical flux planes for three different internodal conductance averaging schemes are plotted as a function of time. The geometric mean option is not shown because this option was not used in the PORFLOW simulations, and the results obtained using this option with TRACR3D were intermediate between the results obtained using arithmetic and harmonic averaging.

The original averaging scheme used by TRACR3D resulted in a horizontal-to-vertical flux ratio of approximately 100:1 for this problem. In other words, when the original TRACR3D internodal hydraulic conductivity averaging scheme was used, the flux of water that was laterally diverted around the clay cap was approximately 100 times greater than the flux of water allowed to pass through the clay cap. When arithmetic or harmonic averaging was used, this horizontal-to-vertical flux ratio was reversed.

Steady-state flow fields were obtained within 75 to 100 years of simulation time with both PORFLOW and TRACR3D when arithmetic or harmonic averaging was used. However, a steady-state flow field had still not been achieved after 500 years of simulation time using the original TRACR3D averaging scheme.

Efforts were made to ensure consistency between the parameters that were input to PORFLOW and TRACR3D for this benchmark problem. However, the codes were allowed to adjust time step sizes as needed. Therefore, the differences in the instantaneous fluxes calculated by the codes using the arithmetic or harmonic averaging schemes may be due in part to differences in time step sizes. Both codes require different units for initial and boundary conditions, fluid properties, etc. Therefore, some of the differences between the simulation results might also be attributed to the number of significant figures that were carried through the unit conversions. However, the differences between the results generated by the codes using the same averaging schemes were relatively small and probably negligible compared to the differences that resulted from arithmetic or harmonic averaging versus the original TRACR3D averaging scheme.

Volumetric water content values generated by the different averaging schemes were also compared. The absolute value 1.369×10^{-4} at $t = 500$ years for the maximum difference between the volumetric water content values generated by TRACR3D and PORFLOW using the arithmetic mean of internodal hydraulic conductivities. In contrast, the absolute value was 5.646×10^{-2} at $t = 500$ years for the maximum difference between volumetric water content values generated using TRACR3D with its original averaging scheme and PORFLOW with arithmetic averaging.

Volumetric water content values generated by TRACR3D with its original and arithmetic averaging schemes and PORFLOW with arithmetic averaging are shown in cross section for the modeled domain in Figure H.9. Only the 0.05 and $0.4 \text{ cm}^3/\text{cm}^3$ contours are plotted to provide clarity for these comparisons. For the arithmetic averaging case, only the outline of the clay cap is evident from the results generated by both PORFLOW and TRACR3D. However, for the case using the original TRACR3D averaging scheme, a distinct "spill-over" lobe is shown by the 0.05 contour, which illustrates the lateral diversion of water over the clay cap.

Figure H.8. Instantaneous Fluxes Passing Through a) Horizontal and b) Vertical Flux Planes as a Function of Time for 3 Internodal Hydraulic Conductivity Averaging Schemes for Benchmark Problem 1

Figure H.9. Volumetric Water Content at $t = 500$ Years for Benchmark Problem 1

The results of this benchmark problem confirmed the hypothesis that differences in the results generated by TRACR3D and PORFLOW for simulations with heterogeneous material properties can be attributed primarily to different intermodal conductance averaging schemes. With respect to transport simulations for the performance assessment, higher water fluxes passing directly through the clay cap, obtained using arithmetic averaging, translated into a potential for greater simulated releases of contaminants from the underlying grout waste form.

Results of a literature review indicated that none of the commonly used averaging schemes for unsaturated flow modeling are necessarily accurate with relatively coarse grids for all conditions. The differences between results generated using the different averaging schemes become less pronounced with finer discretization, although at additional computational expense. To obtain comparable simulation results with the TRACR3D and PORFLOW codes, and to minimize computer CPU time, the arithmetic averaging option was adopted for use in the performance assessment simulations.

H.5.5 Benchmark Test Problem 2

Benchmark problem 2 represented a full-sized performance assessment flow and transport problem. The modeled domain represented a 34.9-m-wide by 85.35-m-high cross section, extending from the assumed postclosure position of the water table to the ground surface at the Grout Treatment Facility. This cross section is depicted in Figure H.10.

The finite difference grid used by TRACR3D for benchmark problem 2 is shown in Figure H.11. This grid consists of 77 nodes in the horizontal direction and 162 nodes in the vertical direction, for a total of 12,474 nodes in the active computational domain. As noted previously, the TRACR3D and PORFLOW codes use block-centered and node-centered discretization schemes, respectively. Therefore, the finite difference grid used for the PORFLOW simulations was slightly different than the grid shown in Figure H.11. However, both grids were designed with same-size "hot grout" areas (Figure H.10) so that both codes would start with identical initial volumes of contaminant. Minimum and maximum node spacings of approximately 0.1 and 1.0 m were used for both grids, and a minimum of 3 nodes was used to represent the thickness of any given material. The finite difference grids were also designed to prevent the distance between adjacent nodes from increasing or decreasing by more than a factor of approximately 2.

A flux of water corresponding to a recharge rate of 0.1 cm/yr was specified for the upper surface of the modeled domain. A fixed concentration equal to 0.0 was also specified for the upper boundary. The lower boundary was held at a pressure head equal to 0, corresponding to a water table at atmospheric pressure. A zero-concentration-gradient boundary condition was also specified for the lower boundary. The side boundaries were specified as no-flow and zero-concentration-gradient boundaries, based on symmetry considerations.

Figure H.10. Modeled Cross Section for Benchmark Problem 2

Figure H.11. Finite Difference Grid for Benchmark Problem 2

An initial pressure head of approximately -74.9 cm was specified for all the engineered materials and backfill soil. This pressure head corresponded to an assumed volumetric water content of 10% for the backfill soil. The initial pressure heads in the soils underlying the engineered materials and backfill soil were assigned values corresponding to a recharge flux of 0.1 cm/yr under a unit hydraulic gradient.

The initial normalized concentrations for the transport simulations were specified as 0 everywhere, except for the domain region labeled "hot grout" in Figure H.10. An initial normalized concentration of 1.0 was specified for this region.

The material properties used for benchmark problem 2 were similar to those used for the performance assessment simulations, with the exception of the gravel overlying the grout vault, and other modifications to approximate asphalt cracking, and degradation. The material properties assigned to the region labeled "gravel" in Figure H.10 were assigned the values of the backfill soil properties. The saturated hydraulic conductivities, van Genuchten model water retention parameters, and bulk densities for these materials are listed in Table H.3. The hydraulic and transport properties assigned to cold grout and hot grout are identical.

The change from gravel to backfill soil properties in the region of the model domain overlying the grout vault was necessary because the gravel properties create a capillary break, which laterally diverts water over the gravel. This lateral diversion of water creates very high velocities in this region of the domain. The S301 code automatically checks Courant numbers. This code also forces the time

Table H.3. Hydraulic Parameters for Benchmark Problem 2

Material	K_s (cm/s)	θ_s	θ_r	α (cm ⁻¹)	n	ρ_b (g/cc)
Hanford Formation						
Sandy sequence	1.55×10^{-3}	0.4203	0.0234	0.1943	1.868	1.68
Gravel sequence	2.73×10^{-4}	0.3584	0.0213	0.0290	1.613	1.73
Ringold Formation	2.42×10^{-6}	0.4982	0.0283	0.0176	1.338	1.45
Backfill Soil	3.00×10^{-2}	0.3710	0.0450	0.0683	2.080	1.65
RCRA Clay Cap	1.00×10^{-7}	0.4480	0.0000	5.39×10^{-4}	1.324	1.45
DSSF Grout	1.47×10^{-8}	0.5781	0.0000	1.08×10^{-5}	1.650	1.10
Concrete	3.75×10^{-10}	0.2258	0.0000	7.61×10^{-6}	1.393	1.98
Asphalt ^(a) 1	1.00×10^{-20}	0.162	0.0000	1.00×10^{-7}	2.000	1.75
Asphalt 2	3.00×10^{-2}	0.202	0.0450	0.0683	2.080	1.38

(a) Asphalt 1 and 2 refer to the hydraulic parameters assigned to the asphalt at $t \leq 90,000$ yr and $t > 90,000$ yr, respectively.

steps to be small enough to satisfy the Courant condition ($Cn \leq 1$) over the entire modeled domain, ensuring stability of the explicit solution scheme. The high velocities in the gravel overlying the grout vault forced the time steps used by the S301 code to be too small to allow conduct of simulations within a reasonable amount of time. Therefore, for the purposes of these benchmark comparisons, the hydraulic properties in the region of model domain representing gravel were simply changed to the properties of the backfill soil, which allowed for much larger time steps. For the performance assessment simulations, the contaminants are located in the grout itself, below the gravel. Therefore, large Courant or Peclet numbers in the gravel overlying the grout vault were considered to be relatively insignificant.

To simulate contaminant transport, the adsorption behavior of various radioactive species in the different materials was represented using distribution coefficients, R_d , which are defined as:

$$R_d = \frac{\text{amount of radionuclide adsorbed on solid per g solid}}{\text{amount of radionuclide in solution per mL of solution}} \quad (21)$$

The distribution coefficient is related to the retardation factor, R_f , as:

$$R_f = 1 + (\rho_b/e)R_d \quad (22)$$

where ρ_b is the dry bulk density (M/L^3), and e is the porosity. The porosity was assumed equivalent to the saturated water content, θ_s .

The retardation factor represents the ratio of the mean water velocity to the mean contaminant velocity in the porous medium. The porosity or saturated water content was used for calculating retardation factors to conservatively estimate solute mobilities, even though most of the materials in the performance assessment simulations are unsaturated.

Three different cases or "bins" were simulated. These bins represented groupings of radioactive species having similar retardation behavior, without directly accounting for specie half-lives. The parameters for Bin 1A conservatively represented species such as ^{129}I and ^{106}Ru . The parameters for Bins 2A and 2B conservatively represented species such as ^{99}Tc and ^{94}Nb , respectively. Transport parameters for the different material types and bin numbers selected for this benchmark problem are shown in Table H.4.

It was assumed that no contaminants are attenuated in the concrete vault or in the asphalt diffusion barrier. Therefore, the distribution coefficients and retardation factors for all contaminants in these materials were assigned values of $R_d = 0.0$ and $R_f = 1.0$, respectively.

Table H.4. Retardation Factors and Distribution Coefficients for Benchmark Problem 2

Bin	$\theta TD_m^{(a)}$	Grout R_f	Soil R_d	Species
1A	5.781×10^{-7}	1.0	0.0	^{129}I , ^{106}Ru
2A	5.781×10^{-7}	4.8	0.0	^{99}Tc
2B	5.781×10^{-7}	4.8	0.67	^{94}Nb

(a) θ = 0.5781 (volume fraction pore water in grout)

T = 0.04 (tortuosity factor)

D_m = $2.5\text{E-}5$ cm^2/s (coefficient of molecular diffusion).

Dispersivities were set equal to 0 for all material types in this benchmark problem and in the performance assessment simulations. Effective diffusion coefficients for the different material types were assumed to be a function of volumetric water content, θ , following the empirical relationship of Kemper and van Schaik (1966):

$$D_e(\theta) = D_m \cdot a \cdot \exp(b\theta) \quad (23)$$

where a and b are empirical constants.

Data from Olsen, Kemper, and van Schaik (1965) and Porter et al. (1960) for soils using NaCl as the diffusing species fit the exponential equation fairly well, with " b " = 10 and " a " as a function of soil surface area. Olsen and Kemper (1965) cite values of " a " ranging from 0.005 to 0.001 for soils ranging in texture from sandy loam to clay. For this benchmark problem and the performance assessment simulations, the values of " a " and " b " were selected as 0.005 and 10, respectively. The diffusion coefficient parameters used for the different material types are shown in Table H.5. Note that for grout, concrete, and asphalt (prior to 90,000 years), the values of " a " and " b " listed in Table H.5 are 1 and 0, respectively. Hence, the effective diffusion coefficients are modeled as independent of volumetric water content for these materials.

Table H.5. Effective Diffusion Coefficients Used for Benchmark Problem 2 and Performance Assessment Simulations

Material	D_m (cm ² /s)	a	b
Hanford Fm, Sands	2.5×10^{-5}	0.005	10
Hanford Fm, Gravels	2.5×10^{-5}	0.005	10
Ringold Fm	2.5×10^{-5}	0.005	10
Backfill Soil	2.5×10^{-5}	0.005	10
Grout	1.0×10^{-10}	1.000	0
Concrete	5.0×10^{-8}	1.000	0
RCRA Clay Cap	2.5×10^{-5}	0.005	10
Asphalt ^(a) 1	1.0×10^{-10}	1.000	0
Asphalt 2	2.5×10^{-5}	0.005	10

(a) Asphalt 1 and 2 refer to parameters for $t \leq 90,000$ yr, and $t > 90,000$ yr, respectively. (See note below regarding time-dependent effective diffusion coefficients.)

The effective diffusion coefficients representing the asphalt diffusion barrier were modified as a function of time to approximate the expected degradation of the asphalt. The time-dependent, effective diffusion coefficient, D_t , was assumed to change according to the following equation:

$$\begin{aligned}
 D_t &= D_e / [1 - (1 - 1 \times 10^{-6}) (t/90000)] & t \leq 90,000 \text{ yr} \\
 D_t &= D_e & t > 90,000 \text{ yr}
 \end{aligned}
 \tag{24}$$

where t is time in years and all other parameters have already been defined. The rates of degradation and change to a constant effective diffusion coefficient after 90,000 years were arbitrarily selected for this benchmark problem. Some of the mechanisms expected to contribute to this degradation include oxidation, volatilization, polymerization, and biodegradation. Measurements of biodegradation rates in asphalt were made after this benchmark problem was simulated and are described in the main performance assessment document.

It was also assumed that the concrete vault and asphalt diffusion barrier will eventually develop cracks or stress fractures from seismic events or overburden pressure, for example. The exact sizes and locations of these cracks or fractures are unknown. However, the concrete vault was designed so that primary cracks likely to develop will be located in the corners of the vault.

A simplified representation of cracks in the concrete vault and asphalt-concrete diffusion barrier was developed. A horizontal row of grid blocks in each of the lower corners of the vault was assigned the same flow and transport parameters as the backfill soil to represent hypothetical cracks in the lower corners of the vault and diffusion barrier. Each row extended outward from the "hot grout" through the concrete vault and asphalt diffusion barrier to the backfill soil. A vertical column and horizontal row of grid blocks in each of the upper corners, extending outward from the "cold grout" through the concrete vault and asphalt diffusion barrier, were also assigned the properties of the backfill soil to represent hypothetical cracks in the upper corners of the vault and diffusion barrier. The grid blocks for these cracks were 10 cm wide. The hypothetical cracks and hydraulic properties assigned to them were considered to be conservative. However, the equivalent hydraulic properties of the materials in the vicinity of these cracks are highly uncertain and likely to change with time.

Three different transport cases were simulated to represent the different bins. The time domain for the simulations was extended until the outflow concentrations at the lower boundary of the model domain had reached their peak values. Contour plots of average relative concentrations at the water table are shown in Figures H.12, and H.13 for the Bin 1A simulations at times of 1000 and 10,000 years, respectively. These figures show excellent agreement between the results generated by the PORFLOW and TRACR3D/S301 codes. The effects of the hypothetical cracks are clearly evident and show that the waste inventory is depleted the fastest near the corners of the vault.

Contour plots of relative concentration are shown in Figures H.14 and H.15 for the Bin 2A simulations at times of 1000, and 10,000 years, respectively. Again, the results generated from PORFLOW and TRACR3D/S301 are very similar.

The results generated from the Bin 2B simulations at times of 1000, and 10,000 years are shown in Figures H.16 and H.17, respectively. Considering the complexity of this benchmark problem and the differences in numerical solution techniques, the agreement between the PORFLOW and TRACR3D/S301 results is considered excellent.

Log-transformed grid Peclet numbers generated from the S301 code using the saturation and velocity fields from TRACR3D at a time of 5000 years are shown in Figure H.18 for the upper 25.34 m of the modeled domain. The top half of Figure H.18 shows the approximate range of grid Peclet numbers generated from this simulation. The locations of the hypothetical cracks through the reinforced concrete and asphalt-concrete are evident. In the lower half of Figure H.18, only the grid Peclet numbers >2 are shown ($\text{Ln } 2 = 0.693$).

The finite difference grid for this problem was designed so that the grid Peclet numbers would be <2 over the entire modeled domain, before the cracking effects were considered. The Peclet number maps shown in Figure H.18 suggest the cracks that were embedded within the model domain are inducing high velocities and creating large grid Peclet numbers within the domain area representing the

Figure H.12. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 1A at $t = 1000$ Years

Figure H.13. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 1A at $t = 10,000$ Years

Figure H.14. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 2A at $t = 1000$ Years

Figure H.15. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 2A at $t = 10,000$ Years

Figure H.16. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 2B at $t = 1000$ Years

Figure H.17. Normalized Concentration Profiles from PORFLOW and TRACR3D/S301 for Bin 2B at $t = 10,000$ Years

Figure H.18. Log-Transformed Grid Peclet Numbers from TRACR3D/S301 for Benchmark Problem 2 at $t = 5000$ Years

grouted waste form. This suggests that further grid refinement in the region of the domain representing the grouted waste form may be required (depending on the specific hydraulic properties that are assigned to the cracks) to reduce possible inaccuracies in peak arrival times and concentrations resulting from numerical diffusion.

As stated previously, the cracks appeared to be the primary feature controlling simulated contaminant releases from the grout vault for this case. Therefore, an accurate representation of these cracks was essential.

Average relative concentrations as a function of time at the water table are shown in Figure H.19 for the Bin 1A, 2A, and 2B simulations. These outflow concentrations also show excellent agreement between the PORFLOW and TRACR3D/S301 codes. Note that the TRACR3D/S301 results only show partial simulations (i.e., they were not run out as far in time as the PORFLOW simulations). The second peaks in the bimodal arrival distribution curves for Bins 2A and 2B reflect the assumed complete degradation of the asphalt-diffusion barrier at a time of 90,000 years.

H.6 Conclusions

Selected verification and benchmark problems were simulated using the PORFLOW, TRACR3D, and S301 computer codes to test the ability of the codes to accurately solve unsaturated flow and transport problems of the type required for the performance assessment.

Simulation results of a simple, two-dimensional flow verification problem using both the PORFLOW and TRACR3D codes showed good to excellent accuracy based on RRMS error calculations. Simulation results generated using both the PORFLOW and S301 codes for a simple, two-dimensional solute transport verification problem were judged to be of acceptable accuracy when the grid Peclet number was close to 2 (2.222). The transport results from both codes showed unacceptable accuracy for larger grid Peclet numbers (80 and 2222), based on RRMS error calculations. This unacceptable accuracy was attributed to excessive numerical dispersion.

Although the results of these verification problems generally agreed with the selected analytical solutions, difficulties were encountered in trying to obtain comparable benchmark results from PORFLOW and TRACR3D for more complex problems with heterogeneous materials. These differences made it necessary to modify the original intermodal conductance averaging scheme in the TRACR3D code. Options were added to TRACR3D for calculating intermodal hydraulic conductivities using arithmetic, harmonic, or geometric averaging, or a weighted conductance averaging scheme. The implementations of these averaging schemes were then tested using a simple, two-dimensional flow benchmark problem.

Figure H.19. Average Relative Outflow Concentrations at the Water Table as a Function of Time for Benchmark Problem 2

Nearly identical flow solutions were obtained with PORFLOW and TRACR3D using the same internodal conductance averaging schemes. However, there appears to be no consensus in the literature regarding a general, finite difference, internodal conductance averaging scheme for unsaturated flow modeling that is practical and accurate under all conditions. Therefore, the arithmetic mean was selected for the verification and benchmark problems in this appendix and for all the performance assessment simulations.

After modifying the internodal conductance averaging schemes in TRACR3D, nearly identical results were also obtained using PORFLOW and TRACR3D/S301 for a complex, large-scale, two-dimensional flow and transport benchmark problem. This benchmark problem used the same computational grid and most of the hydraulic and transport parameters that were used for the performance assessment simulations. The hydraulic properties of hypothetical cracks embedded within the model domain appeared to be the primary (most sensitive) parameters controlling the simulated release of contaminants from the waste form. Therefore, an accurate representation of these cracks is essential. Considering the complexity of this benchmark problem and the differences in the numerical approximations used by the different codes, the similarity of the results obtained for benchmark problem 2 was considered excellent.

Extensive grid convergence tests were not conducted for the benchmark problems because of the excessive CPU time already required for the large-scale simulations. Therefore, the effects of possible solution inaccuracies resulting from inadequate spatial discretization have not been quantified. However, the grid Peclet numbers for the benchmark problem 2 and for the low recharge cases (0.1 cm/yr) in the performance assessment simulations are <2 over most of the modeled domain. Therefore, these results are assumed to be reasonably close to the "true" numerical solutions.

Because of the difficulties in accurately solving large-scale, advection-dominated transport problems using standard finite difference and finite element methods, mixed Eulerian-Lagrangian solution methods have been developed, such as that incorporated in the S301 code. The particle-tracking feature of the S301 code was specifically designed to correct for artificial numerical dispersion in high grid Peclet number problems, but was found to be impractical for the large-scale performance assessment simulations because it required excessive computational time. Other numerical approaches, such as flux corrected transport schemes (Zalesek 1978), should be investigated as possible alternatives. Recent advances in computer hardware, such as high-speed, massively parallel computers, should also allow large-scale, transient unsaturated flow and transport problems to be simulated efficiently and accurately, with much higher resolution than is currently practical with conventional computational platforms (Dougherty 1991). The higher resolution and speed attained using parallel processing will help eliminate some of the difficulties associated with using standard finite difference and finite element methods to simulate large-scale, transient, unsaturated flow and transport problems.

H.7 References

- Abramowitz, M., and I. A. Stegun. 1964. *Handbook of Mathematical Functions*, Vol. 55. Nat. Bur. Stand., Appl. Math. Ser. U.S. Government Printing Office, Washington, D.C.
- Bear, J. 1972. *Dynamics of Fluids in Porous Media*. Elsevier, New York.
- Brutsaert, W. F. 1971. "A Functional Iteration Technique for Solving the Richards Equation Applied to Two-Dimensional Infiltration Problems." *Water Resour. Res.* 7:1583-1596.
- Bouloutas, E. T. 1989. "Improved Numerical Methods for Modeling Flow and Transport Processes in Partially-Saturated Porous Media." Ph.D. Dissertation. Massachusetts Institute of Technology, Boston, Massachusetts.
- Carslaw, H. S., and J. C. Jaeger. 1959. *Conduction of Heat in Solids*. Oxford University Press, New York.
- Celia, M. A., L. R. Ahuja, and G. F. Pinder. 1987. "Orthogonal Collocation and Alternating-Direction Procedures for Unsaturated Flow Problems." *Adv. Water Resour.* 10:178-187.
- Chiang, C. Y., M. F. Wheeler, and P. B. Bedient. 1989. "A Modified Method of Characteristics Technique and Mixed Finite Element Method for Simulation of Groundwater Solute Transport." *Water Resour. Res.* 25:1541-1549.
- Cleary, R. W., and M. J. Unger. 1978. *Analytical Models for Groundwater Pollution and Hydrology*. Report 78-WR-15. Water Resources Program, Department of Civil Engineering, Princeton University, Princeton, New Jersey.
- Dougherty, D. E. 1991. "Hydrologic Applications of the Connection Machine CM-2." *Water Resour. Res.* 27:2137-3147.
- Farmer, C. L. 1985. "A Moving Point Method for Arbitrary Peclet Number Multi-Dimensional Convection-Diffusion Equations." *IMA Journal of Numerical Analysis* 5:465-480.
- Gardner, W. H. 1958. "Some Steady State Solutions to the Unsaturated Moisture Flow Equation with Application to Evaporation from a Water Table." *Soil Sci.* 85:228-232.
- Haverkamp, R., and M. Vauclin. 1979. "A Note on Estimating Finite Difference Interblock Hydraulic Conductivity Values for Transient Unsaturated Flow Problems." *Water Resour. Res.* 15:181-187.

Huyakorn, P. S., and G. F. Pinder. 1983. *Computational Methods in Subsurface Flow*. Academic Press, Orlando, Florida.

International Math Subroutine Library (IMSL). 1987. *IMSL User's Manual, Version 1.0, Math/Library FORTRAN Subroutines for Mathematical Applications*. Houston, Texas.

Kemper, W. D., and J. C. van Schaik. 1966. "Diffusion of Salts in Clay Water Systems." *Soil Sci. Soc. Am. Proc.* 30:534-540.

Magnusen, S. W., R. G. Baca, and A. J. Sondrup. 1990. *Independent Verification and Benchmark Testing of the PORFLO-3 Computer Code, Version 1.0*. EGG-BG-9175, Idaho National Engineering Laboratory, Idaho Falls, Idaho.

Olsen, S. R., and W. D. Kemper. 1965. "Movement of Nutrients to Plant Roots." *Adv. Agron.* 30:91-151.

Olsen, S. R., W. D. Kemper, and J. C. van Schaik. 1965. "Self-Diffusion Coefficients of Phosphorus in Soil Measured by Transient and Steady-State Methods." *Soil Sc. Am. Proc.* 29:154-158.

Patankar, S. V. 1980. *Numerical Heat Transfer and Fluid Flow*. McGraw-Hill, New York.

Piepho, M. G., W. H. Sutherland, P. D. Rittman, and F. M. Mann. 1993. *The Grout Performance Assessment Code System (GPACS) with Verification and Benchmarking*. WHC-SD-WM-UM-019, Westinghouse Hanford Company, Richland, Washington.

Porter, L. K., W. D. Kemper, R. D. Jackson, and B. C. Stewart. 1960. "Chloride Diffusion in Soils as Influenced by Moisture Content." *Soil Sc. Soc. Am. Proc.* 24:460-463.

Richards, L. A. 1931. "Capillary Conduction of Liquids in Porous Mediums." *Physics* 1, 318-333.

Runchal, A. K., and B. Sagar. 1992. *PORFLOW: A Model for Fluid Flow, Heat, and Mass Transport in Multifluid, Multiphase, Fractured or Porous Media - Users Manual, Version 2.4*. ACRi/016/REV.G, Analytical and Computational Research, Inc., Los Angeles, California.

Scheidegger, A. E. 1961. "General Theory of Dispersion in Porous Media." *J. Geophys. Res.* 66:3273-3278.

Schnabel, R. R., and E. B. Ritchie. 1984. "Calculation of Internodal Conductances for Unsaturated Flow Simulations: A Comparison." *Soil Sci. Soc. Am. J.* 48:1006-1010.

Thomas, T. R. 1991. *Solute Transport Benchmark Studies for TRACR3D Code Verification*. WINCO-1083, Idaho National Engineering Laboratory, Idaho Falls, Idaho.

Travis, B. J., and K. H. Birdsell. 1991. *TRACR3D: A Model of Flow and Transport in Porous Media*. LA-11798-M, Los Alamos National Laboratory, Los Alamos, New Mexico.

Trent, D. S. 1975. *Mathematical Modeling of Transport Processes in Aquatic Systems*. BNWL-SA-5379, Pacific Northwest Laboratory, Richland, Washington.

van Genuchten. 1980. "A Closed Form Equation for Predicting the Hydraulic Conductivity of Unsaturated Soils." *Soil Sc. Soc. of Am. J.* 44:892-898.

Warrick, A. W. 1974. "Time-Dependent Linearized Infiltration. I. Point Sources." *Soil Sci. Soc. Am. Proc.* 38:383-386.

Warrick, A. W. 1991. "Numerical Approximations of Darcian Flow Through Unsaturated Soil." *Water Resour. Res.* 27:1215-1222.

Warrick, A. W., and D. O. Lomen. 1976. "Time-Dependent Linearized Infiltration: III. Strip and Disc Sources." *Soil Science Soc. Amer. Proc.* 40:639-643.

Wikramaratna, R. S., and C. L. Farmer. 1987. *The S301 High Resolution Miscible Displacement Simulator, 2-D Version with User-Specified Velocities*. Technical Report S301-2/1. Oil Recovery Projects Division, Winfrith Atomic Energy Establishment, Dorset, United Kingdom.

Zaidel, J., and D. Russo. 1992. "Estimation of Finite Difference Interblock Conductivities for Simulation of Infiltration Into Initially Dry Soils." *Water Resour. Res.* 28:2285-2295.

Zalesak, S. T. 1978. "Fully Multidimensional Flux-Corrected Transport Algorithms for Fluids." *J. Comp. Phys.* 31:335-362.

Appendix I

GENII Computer Code

Appendix I

GENII Computer Code: Description Of The GENII and GENII-S Computer Codes

K. Rhoads and S. F. Snyder, Pacific Northwest Laboratory

The GENII computer code version 1.485 (Napier et al. 1988) was used to perform the environmental accumulation and dose assessment calculations for all exposure scenarios except the drinking water dose assessment. GENII (GENeration II), the second generation of Hanford Environmental Dosimetry System computer codes, was originally developed for environmental pathway analyses at Hanford. It has been used for several years to perform dose calculations for the Hanford Site Annual Environmental Report as well as for other routine assessments of Hanford facilities. Because GENII was developed specifically for environmental accumulation and dose estimate calculations for the Hanford region, use of this code is most appropriate for the performance assessment.

The GENII computer code was developed at Pacific Northwest Laboratory (PNL)^(a) to incorporate the internal dosimetry models recommended by the International Commission on Radiological Protection (ICRP 1977, 1979-1988, 1986) into updated versions of existing environmental pathway analysis models. The GENII system was developed to provide a state-of-the-art, technically peer-reviewed, documented set of programs for calculating radiation doses from radionuclides released to the environment. Although the codes were developed for use at Hanford, they were designed with the flexibility to accommodate input parameters for a wide variety of generic sites.

The system includes the capabilities for calculating radiation doses for acute releases, with options for annual dose, committed dose, and cumulative dose; for calculating the same types of doses from chronic releases; for evaluating exposure pathways including direct exposure via water (swimming, boating, and fishing), soil (surface and buried sources), air (semi-infinite cloud and finite cloud geometries), inhalation, and ingestion pathways. The release scenarios include acute releases to air from ground level or elevated sources, or to water; and initial contamination of soil or surfaces. Source term variations include decay of radionuclides to the start of the exposure scenario, input of total radioactivity or specified fractions, and input of measured concentrations in specified environmental media. Interfaces are provided for external calculations of atmospheric dispersion.

(a) Pacific Northwest Laboratory is operated by Battelle Memorial Institute for the U.S. Department of Energy under Contract DE-AC06-76RLO 1830.

geohydrology, biotic transport, and surface water transport. Target populations are identified by distance and direction for individuals, populations, and for intruders into contained sources. To accommodate the initial requirements on the design of the codes, the Hanford Environmental Dosimetry System was written to determine radiation doses to individuals or populations from a wide variety of potential exposure scenarios. The core system may be used to calculate annual doses, dose commitments, or accumulated doses from acute or chronic releases of radioactive materials to air or water.

The Hanford Environmental Dosimetry System (GENII) is composed of seven linked computer codes and their associated data libraries. These codes and their linkages are illustrated in Figure I.1. The computer programs are of three types: user interfaces (i.e., interactive, menu-driven programs to assist the user with scenario generation and data input), internal and external dose factor generators, and the environmental dosimetry programs. For maximum flexibility, the portion of the code used for an analysis of short-term scenarios (as opposed to 10,000-year migration analyses) has been divided into three interrelated but separate exposure and dose calculations, respectively.

GENII is described in three volumes of documentation (Napier et al. 1988). Volume 1 describes the theoretical considerations of the system, including conceptual diagrams, mathematical representation of the solutions, and descriptions of solution techniques, where appropriate. The second volume is a Users' Manual, providing code structure, users' instructions, required system configurations, and topics related to quality assurance (QA). The third volume is a Code Maintenance Manual for the user who requires knowledge of code detail, including code logic diagrams, global dictionary, worksheets, example hand calculations, and listings of the code and its associated data libraries.

I.1 Quality Assurance Requirements for the GENII Computer Code

The GENII software package was developed under a QA framework that implemented the requirements of ANSI/ASME NQA-1 (ASME 1986). NQA-1 specifies that the following items be addressed for hardware design control:

- design input
- design process, including design analysis
- design verification
- change control
- interface control
- documentation and records.

Figure I.1. Component Programs of the GENII Software Package

The QA procedures applied during development of the GENII code were an interpretation of the NQA-1 hardware requirements for software. The software design process consisted of developing and internally testing software in accordance with the design input. The GENII package has been extensively tested and verified by hand calculations and benchmarked against similar Hanford environmental dosimetry programs. Also, the models implemented by the code have undergone technical review by an external panel of experts.

I.2 Performance Assessment Use of GENII

GENII was used in this performance assessment to produce estimates of

- external exposure doses from radionuclides in groundwater, surface water, surface soil, and buried waste
- inhalation doses from resuspended material

- ingestion doses from intakes of contaminated water, food crops, animal products (e.g., meat, eggs), and inadvertently consumed soil.

All pathway dose estimates are essentially the product of radionuclide concentration in the medium of interest (i.e., air, water, or food); the intake rate via ingestion and inhalation or exposure time for external exposure; and the appropriate dose conversion factor (DCF). The appropriate combination of pathway algorithms (external exposure, inhalation, or ingestion) was activated for each scenario. A brief description of how each pathway is modeled in GENII is provided in Section I.4.

Values for many input parameters needed to produce GENII dose estimates are specified by the user as part of the scenario definition process. Default values for a number of other parameters are incorporated directly into the GENII code or into data files that are generally not modified by the user (e.g., the GENIDEFAULT.IN file). Parameters that are common to several scenarios are discussed in Section I.5; parameters specific to each scenario are tabulated in the individual scenario discussions (see Appendix J).

Rather than using the GENII code to produce final dose estimates, the code was used to generate "scenario dose factors" (scenario DFs) based on unit radionuclide concentrations in grout, groundwater, or surface water. This approach was used because development of the waste inventory and groundwater transport modeling were done concurrently with scenario development. Scenario DFs were used to calculate dose to the receptor by multiplying the final concentration in waste or environmental media by the radionuclide-specific DF.

To derive a scenario DF, it was assumed that a unit activity of a given radionuclide was contained in grout, soil, or the downgradient water supply. External exposure, inhalation, and ingestion dose estimates for unit concentrations of each relevant radionuclide were then calculated using GENII. The scenario DFs also include the dose contributions from buildup of radioactive progeny following decay of parent nuclides in the media of interest.

I.3 The GENII-S Computer Code

In addition to the GENII code, GENII-S (Leigh et al. 1992) was used to determine the sensitivity of dosimetry results to the exposure pathway and dosimetry parameters used for this PA. GENII-S is a modified version of the GENII code that maintains the original software algorithms incorporated into a sensitivity and uncertainty analysis software (SUNS) shell. Implementation of the SUNS shell gives the user the capability to perform sensitivity analyses in a single operation, thereby eliminating the need for manual interfaces between the results of multiple GENII calculations and an independent sensitivity analysis software package.

GENII-S allows the user to specify ranges for variable parameters along with their associated probability density functions (PDFs). Permissible types of PDFs within the code include uniform,

log-uniform, triangular, normal, and lognormal. The code selects random values for each variable using a Latin hypercube sampling technique based on the user-specified parameter ranges and distributions. The GENII software is then run for a predetermined number of trials using a different set of randomly selected variables for each run. The results of the trials are compiled into a cumulative distribution function, and other statistical analyses are also available to determine the interdependence of various parameters in the calculation. A discussion of PDF selection can be found in Snyder et al. 1994. Ranges for the variable parameters and their associated PDFs used in this analysis are listed in Appendix Q.

I.4 GENII Exposure Pathways

Following shallow-land burial, several pathways may account for an individual's exposure to radioactive materials, including external exposure, inhalation, and ingestion. All of the internal dose estimates reported in this analysis represent a 50-year committed dose resulting from intake during a single year. A summary of the GENII exposure pathway models are presented in the following sections. A more detailed description of the GENII modelling approach can be found in the code documentation (Napier et al. 1988).

I.4.1 GENII External Exposure Dose Models

External exposure in this performance assessment is the result of exposure to penetrating radiation from radionuclides in contaminated surface soil and the grout vaults themselves. External doses from surface soil are the result of either exhumation of a portion of the grout during well drilling or contamination that results from irrigation water applications. The dose from surface soil exposure considers uniform distribution of radionuclides in the upper 15 cm of soil, depletion of the initial radionuclide concentration by radioactive decay, and depletion by leaching of radionuclides in the plow layer to deeper soil layers over the growing season.

Dose estimates for penetrating radiation from the buried grout are modelled to account for attenuation by the 5-m layer of soil above the grout vaults. No external doses were calculated from resuspended soil because they are negligible compared to other pathways. Two components of the external exposure dose calculation - finite area corrections and indoor and outdoor exposures - require more detailed discussion in the following sections.

I.4.1.1 Finite Area Contamination

An external exposure correction factor is included in the calculations for external doses from small areas of contaminated ground. Areas larger than 1250 m² are considered to be an "infinite plane" source, whereas smaller areas require use of a dose rate reduction factor. The code data library contains surface contamination DFs for an infinite plane source, and they must be adjusted by the reduction factor if the contaminated area is sufficiently small. A dose rate reduction factor was used

only in the driller scenario because contamination was assumed to be limited to an area 100 m². The external ground surface dose factors used for this analysis were also based on the assumption that contamination was uniformly mixed in the top 15 cm of soil.

I.4.1.2 Indoor and Outdoor Exposure

The exposure time to soil contamination used for external exposure dose calculations in the post-drilling, irrigated farm, and Columbia River scenarios warrants clarification. Radionuclides in the upper soil layers present a pathway for external exposure. If an individual is outdoors at all times, the dose calculation is relatively straightforward. However, individuals located indoors have a reduced exposure to penetrating radiation from radionuclides in the soil because of increased distance and shielding by building materials. For the purposes of this PA, individuals are assumed to spend a portion of their time indoors.

External exposure dose estimates can be calculated by considering the indoor and outdoor exposure periods separately, or alternatively as done for this PA, as an "effective outdoor exposure time." The calculation of the effective outdoor exposure time is shown in Equation 1.

$$t_{\text{out,eff}} = t_{\text{out}} + (t_{\text{in}} \cdot S) \quad (1)$$

where $t_{\text{out,eff}}$ = effective outdoor exposure time

t_{out} = time spent outdoors, h/yr

t_{in} = time spent indoors, h/yr

S = shielding factor, dimensionless

Each parameter in the above equation is subject to substantial uncertainty. The amount of time spent outdoors depends on weather, demographic characteristics, and personal preferences. The shielding factor depends on the radioisotope content of the upper soil layer and building construction (both design and materials). The assumptions used for this PA are based on an effective outdoor exposure time of 0.5, which would be equivalent to the following assumptions:

$$t_{\text{out}} = 789 \text{ h}$$

$$t_{\text{in}} = 7977 \text{ h}$$

$$S = 0.45$$

I.4.1.3 Scenario External Exposure Doses

Sources of external exposure to radionuclides include both the buried grout and the radionuclides transported to the upper soil layer. The following lists the external dose contributors used for each scenario:

Scenario	External dose from
Driller	Buried grout, upper soil layer
Post-driller	Buried grout, upper soil layer (effective outdoor exposure)
Irrigated farm	Upper soil layer (effective outdoor exposure)
Columbia River	Upper soil layer (effective outdoor exposure)
Drinking water	No external dose

No external doses were calculated for resuspended soil, because screening calculations indicated that external doses from resuspended materials were 5 orders of magnitude lower than those from the upper soil layer. Therefore, neglect of this pathway does not affect the external doses estimated for the PA.

I.4.2 GENII Inhalation Dose Model

Internal doses may result from inhalation of radionuclides resuspended from the soil surface by wind or other mechanical disturbance. A mass loading model was used to approximate the radionuclide concentrations in airborne particulates by assuming the particulate concentrations were equivalent to the radionuclide concentrations in soil. Instantaneous equilibrium between the activity in soil and airborne particulates was assumed. Individuals were assumed to inhale contaminated air at the rate of 8520 m³/yr, a value consistent with inhalation rates for the reference man (ICRP 1975). All scenarios except the drinking water scenario evaluate the inhalation dose from soil resuspension.

I.4.3 GENII Ingestion Dose Models

Internal doses can also result from the intake via ingestion of contaminated water, food crops, animal products, and soil. The radionuclide concentrations in food products are calculated by the GENII code from their concentrations in soil or in water (surface- or groundwater) used for irrigation or direct consumption.

Ingestion of radioactive materials via food crops may result from root uptake, irrigation with contaminated water, and soil resuspension with subsequent deposition onto leaves. Radionuclide concentrations in food crops following root uptake are calculated using concentration ratios (CRs), which are empirically determined estimates of radionuclide concentrations in plants based on the radionuclide

concentration in soil. External contamination of the food crop via deposition of resuspended soil or irrigation water is determined using an interception fraction, which is related to the above-ground biomass for each type of crop.

Radioactive materials ingested by animals via contaminated water and feed subsequently become incorporated into edible products (meat, milk, eggs) consumed by humans. Radionuclide concentrations in animal products are calculated from the rates of intake by animals multiplied by a transfer factor. The transfer factor is an empirical quantity that relates the animal's radionuclide intake rate to the concentration ultimately found in edible products. Again, instantaneous equilibrium is assumed between the radionuclide concentrations in animal feed and water and that in the edible food products.

1.5 Databases used by GENII

This section describes and lists parameters used in the GENII code. Radionuclide-dependent (e.g., dose conversion factor) and element-dependent (e.g., concentration ratio) data are distributed with the code in the form of text or binary data libraries. Some of the values for parameters in the default databases distributed with the GENII code were replaced with alternate values for use with this analysis. The alternative databases were developed either to incorporate updated parameter values or to substitute values that better represent scenario-specific pathways and conditions.

1.5.1 Dose Conversion Factors

Dose conversion factors (DCFs) are radionuclide-specific parameters that represent the dose resulting from a unit intake or exposure to a unit-concentration source of a given radionuclide. Five different types of radionuclide DCFs are used to calculate the final scenario DFs for this analysis. Inhalation and ingestion DCFs represent the internal dose following intake of a unit quantity of radionuclides via each pathway. External DCFs include the external dose from radionuclides per unit concentration in surface soil, buried waste, or immersion in water. The dose from external sources depends on the radionuclide concentration in the source medium, its geometry with respect to the receptor, the type and quantity of shielding material (if any), and the time over which the individual is exposed to the source. Listings of both external and internal dose conversion factors have been published by the U.S. Department of Energy (1988a, 1988b).

1.5.1.1 Internal DCFs

Internal DCFs for the inhalation and ingestion pathways are calculated by the GENII code for a particular exposure and dose commitment period based on models recommended by the International Commission on Radiological Protection in Publications 26, 30, and 48 (ICRP 1977, 1979-1988, and 1986). The GENII libraries for inhalation and ingestion DCFs are provided as incremental dose factors in a binary format to permit calculations for a variable dose commitment period. To display the internal DCFs calculated by the GENII code for a 1-year exposure with a 50-year dose

commitment period, a test scenario was performed to generate a listing of the inhalation and ingestion DCFs for pertinent radionuclides (See Exhibit I.1).

Inhalation and ingestion DCFs depend, in part, on the chemical form of the radionuclide at the time of intake. The chemical forms associated with the maximum DCF values for each radionuclide were used for this analysis because the chemical forms of the radionuclides are either unknown or are subject to change after release from the waste site. For comparison purposes only, the maximum GENII and maximum DOE (1988b) internal DCF values are listed in Exhibit I.1 for all grout inventory radionuclides and their progeny evaluated in this PA. Differences between the maximum GENII and maximum DOE DCFs are the result of minor differences in the derivation method and metabolic model assumptions. Exhibit I.1 shows that the GENII and DOE ingestion and inhalation DCFs generally agree within $\pm 10\%$.

I.5.1.2 External DCFs

External DCFs were used in this PA to determine the dose from exposure to contaminated soil or grout and from immersion in contaminated water. GENII soil surface DCFs represent the dose from a unit concentration of radionuclide uniformly dispersed in the upper 15-cm soil layer, whereas DOE soil-surface DCFs indicate the dose from a unit concentration of radionuclide on the ground surface. The GENII values are somewhat lower than the DOE values because of the added shielding effect of having the radionuclides dispersed through the soil surface layer. Because the PA scenarios involving contaminated soil result from excavation of buried grout or irrigation deposition on cultivated ground (as opposed to air deposition of radionuclides on the soil surface), the GENII soil surface DCFs are more appropriate for this analysis and are used in preference to the DOE soil-surface DCFs.

The water immersion DCFs were used in the Columbia River Scenario for exposure during swimming only. The default water immersion DCFs distributed with the GENII code were calculated by a simplified adaptation of the method used to determine the DOE values (DOE 1988a). For this analysis, a library containing the DOE values for radionuclides evaluated in the Columbia River scenario was substituted for the GENII default library because the DOE DCFs were calculated in a more rigorous manner. These values are shown in Exhibit I.2.

I.5.2 Concentration Ratios and Transfer Factors

Concentration ratios (CRs) are used to estimate the radionuclide concentrations in vegetation from root uptake of radionuclides in soil. Transfer factors (TFs) are used to calculate the animal product contamination levels resulting from animal ingestion of radionuclides via feed and drinking water. The values for CRs and TFs are element dependent rather than radionuclide dependent. For this analysis, the default CR and TF libraries distributed with the GENII code were replaced with a library containing values from Kennedy and Strenge (1992), which are based on a more recent comprehensive literature review (IUR 1989). Most TFs for poultry and eggs in the revised library were identical to

the GENII default values because little new information was available in this area. The Kennedy and Streng CRs and TFs are listed in Exhibit I.3. As in the original GENII library, CR and TF values are not provided for noble gases because they are not concentrated in plant or animal tissues.

Parameters similar to the animal product TFs are used in the Columbia River Scenario to estimate the radionuclide concentrations in fish that inhabit contaminated water. This parameter, the bioaccumulation factor, relates the concentrations of radionuclides in aquatic animals and plants to the concentrations in surrounding water. The GENII default values, listed in Exhibit I.4, were used for freshwater fish, and no other aquatic foods were considered in this analysis. The only element evaluated in the Columbia River Scenario for which a bioaccumulation factor was not available was francium, which results from decay of plutonium-239. However, this radionuclide is not present in large enough quantities to contribute substantially to the dose.

I.5.3 Miscellaneous Default Parameters

A number of input parameters are used to describe regional and demographic conditions (e.g., irrigation rate, food consumption rates, etc.). In the GENII code these parameters are incorporated into the dose calculation via both the "scenario input file" (i.e., the scenario.IN file) and a "default parameter file" (i.e., the DEFAULT.IN file in the distribution version of GENII). Scenario input files are used to provide values for variables that would be expected to change from case to case (see Appendix J), whereas the DEFAULT.IN file contains parameters specific to a particular region, but which remain relatively constant for all types of scenarios.

The default parameter values used for this PA are shown in Exhibit I.5 (driller scenario) and I.6 (post driller, irrigated farm, and Columbia River scenarios). Both default parameter files are equivalent to the original GENII distribution version except for the soil ingestion rates. Although the soil ingestion rates shown in Exhibits I.5 and I.6 differ, the soil ingestion rates used in both scenarios were equivalent to 100 mg/d. Because the exposure period was limited to 5 days in the driller scenario, the total soil ingestion for the driller was equivalent to 100 mg/d for five days. The GENII code models soil ingestion over a 1-year period, therefore an effective soil ingestion rate over the entire year was calculated (as $100 \text{ mg/d} \times 5 \text{ d/yr} \times 1 \text{ yr}/365.25 \text{ d} = 1.37 \text{ mg/d}$) for use in the driller scenario DEFAULT.IN file.

Exhibit I.1. Maximum GENII and DOE Inhalation and Ingestion DCFs for Radionuclides Considered in the Dose Assessment

Inhalation				Ingestion			
Radionuclide	GENII	DOE	G/D ^(a)	Radionuclide	GENII	DOE	G/D
H 3	9.0E - 05	6.3E - 05	1.4	H 3	6.1E - 05	6.3E - 05	1.0
C 14	2.1E - 03	2.1E - 03	1.0	C 14	2.1E - 03	2.1E - 03	1.0
CO 60	2.0E - 01	1.5E - 01	1.3	CO 60	2.6E - 02	2.6E - 02	1.0
NI 63	3.0E - 03	3.0E - 03	1.0	NI 63	5.5E - 04	5.4E - 04	1.0
SE 79	9.5E - 03	8.9E - 03	1.1	SE 79	8.3E - 03	8.3E - 03	1.0
SR 90	2.0E - 01	2.3E - 01	0.9	SR 90	1.2E - 01	1.3E - 01	0.9
Y 90	8.7E - 03	8.2E - 03	1.1	Y 90	1.1E - 02	1.0E - 02	1.1
ZR 95	2.3E - 02	1.9E - 02	1.2	ZR 95	3.7E - 03	3.4E - 03	1.1
NB 95M	2.5E - 03	2.2E - 03	1.1	NB 95M	2.3E - 03	2.0E - 03	1.2
NB 95	5.7E - 03	4.5E - 03	1.3	NB 95	2.5E - 03	2.2E - 03	1.1
NB 94	3.8E - 01	3.3E - 01	1.2	NB 94	7.2E - 03	5.1E - 03	1.4
TC 99	8.6E - 03	7.5E - 03	1.1	TC 99	2.2E - 03	1.3E - 03	1.7
RU 103	9.0E - 03	7.8E - 03	1.2	RU 103	3.0E - 03	2.7E - 03	1.1
PD 103	1.6E - 03	1.4E - 03	1.1	PD 103	7.8E - 04	6.9E - 04	1.1
RH 103M	4.9E - 06	4.6E - 06	1.1	RH 103M	1.2E - 05	1.1E - 05	1.1
RU 106	4.7E - 01	4.4E - 01	1.1	RU 106	2.7E - 02	2.1E - 02	1.3
SN 113	1.1E - 02	8.9E - 03	1.2	SN 113	3.1E - 03	2.7E - 03	1.1
IN 113M	4.2E - 05	3.4E - 05	1.2	IN 113M	1.1E - 04	1.0E - 04	1.1
SB 125	1.2E - 02	9.8E - 03	1.2	SB 125	2.8E - 03	2.6E - 03	1.1
TE 125M	7.2E - 03	6.7E - 03	1.1	TE 125M	3.7E - 03	3.4E - 03	1.1
SN 126	9.8E - 02	8.6E - 02	1.1	SN 126	1.9E - 02	1.7E - 02	1.1
SB 126M	2.9E - 05	2.8E - 05	1.0	SB 126M	9.1E - 05	7.3E - 05	1.2
SB 126	1.2E - 02	1.0E - 02	1.2	SB 126	1.0E - 02	9.6E - 03	1.0
I 129	1.5E - 01	1.8E - 01	0.8	I 129	2.5E - 01	2.8E - 01	0.9
CS 134	4.3E - 02	4.7E - 02	0.9	CS 134	6.8E - 02	7.4E - 02	0.9
CS 135	4.5E - 03	4.5E - 03	1.0	CS 135	6.8E - 03	7.1E - 03	1.0
CS 137	3.0E - 02	3.2E - 02	0.9	CS 137	4.7E - 02	5.0E - 02	0.9
CE 144	3.7E - 01	3.5E - 01	1.1	CE 144	2.1E - 02	2.0E - 02	1.1
PR 144M	1.9E - 05	0.0E + 00	-	PR 144M	4.8E - 05	0.0E + 00	--
PR 144	4.5E - 05	4.2E - 05	1.1	PR 144	1.2E - 04	1.1E - 04	1.1
EU 152	2.1E - 01	2.2E - 01	1.0	EU 152	6.3E - 03	6.0E - 03	1.1
EU 154	2.7E - 01	2.6E - 01	1.0	EU 154	9.2E - 03	9.1E - 03	1.0
EU 155	4.0E - 02	3.9E - 02	1.0	EU 155	1.5E - 03	1.3E - 03	1.2
TH 230	3.2E + 02	3.2E + 02	1.0	TH 230	5.4E - 01	5.3E - 01	1.0
RA 226	8.1E + 00	7.9E + 00	1.0	RA 226	9.5E - 01	1.1E + 00	0.9
RN 222	0.0E + 00	0.0E + 00	--	RN 222	0.0E + 00	0.0E + 00	--

WHC-SD-WM-EE-004, Rev.1
Exhibit I.1. (contd)

Inhalation				Ingestion			
Radionuclide	GENII	DOE	G/D ^(a)	Radionuclide	GENII	DOE	G/D
H 3	9.0E - 05	6.3E - 05	1.4	H 3	6.1E - 05	6.3E - 05	1.0
PB 210	1.4E + 01	1.3 + 01	1.1	PB 210	5.3E + 00	5.1E + 00	1.0
BI 210	2.0E - 01	1.9E - 01	1.1	BI 210	6.3E - 03	5.9E - 03	1.1
PO 210	9.7E + 00	8.1E + 00	1.2	PO 210	1.9E + 00	1.6E + 00	1.2
U 234	1.3E + 02	1.3E + 02	1.0	U 234	2.8E - 01	2.6E - 01	1.1
U 235	1.2E + 02	1.2E + 02	1.0	U 235	2.6E - 01	2.5E - 01	1.0
TH 231	8.3E - 04	8.1E - 04	1.0	TH 231	1.3E - 03	1.3E - 03	1.0
PA 231	1.3E + 03	1.3E + 03	1.0	PA 231	1.1E + 01	1.1E + 01	1.0
AC 227	6.7E + 03	6.7E + 03	1.0	AC 227	1.4E + 01	1.4E + 01	1.0
TH 227	1.6E + 01	1.6E + 01	1.0	TH 227	3.8E - 02	3.6E - 02	1.1
FR 223	7.8E - 03	6.1E - 03	1.3	FR 223	1.1E - 02	8.6E - 03	1.3
RA 223	7.7E + 00	7.5E + 00	1.0	RA 223	2.7E - 01	5.5E - 01	0.5
NP 237	6.4E + 02	4.9E + 02	1.3	NP 237	5.2E + 00	3.9E + 00	1.3
PA 233	9.5E - 03	8.6E - 03	1.1	PA 233	3.6E - 03	3.3E - 03	1.1
U 238	1.2E + 02	1.2E + 02	1.0	U 238	2.6E - 01	2.3E - 01	1.1
TH 234	3.5E - 02	3.3E - 02	1.1	TH 234	1.3E - 02	1.3E - 02	1.0
PA 234	8.5E - 04	7.4E - 04	1.1	PA 234	2.2E - 03	2.1E - 03	1.0
PU 242	4.0E + 02	4.8E + 02	0.8	PU 242	3.3E + 00	4.1E + 00	0.8
NP 238	4.3E - 02	3.1E - 02	1.4	NP 238	4.0E - 03	3.4E - 03	1.2
PU 238	3.9E + 02	4.6E + 02	0.8	PU 238	3.2E + 00	3.8E + 00	0.8
CM 244	2.5E + 02	2.7E + 02	0.9	CM 244	2.0E + 00	2.3E + 00	0.9
PU 244	4.0E + 02	4.8E + 02	0.8	PU 244	3.3E + 00	4.0E + 00	0.8
U 240	2.3E - 03	2.1E - 03	1.1	U 240	4.6E - 03	4.1E - 03	1.1
PU 240	4.3E + 02	5.1E + 02	0.8	PU 240	3.6E + 00	4.3E + 00	0.8
PU 241	8.2E + 00	1.0E + 01	0.8	PU 241	6.8E - 02	8.6E - 02	0.8
AM 241	4.4E + 02	5.2E + 02	0.8	AM 241	3.6E + 00	4.5E + 00	0.8
CM 243	3.1E + 02	3.5E + 02	0.9	CM 243	2.5E + 00	2.9E + 00	0.9
PU 243	1.5E - 04	1.5E - 04	1.0	PU 243	3.2E - 04	3.3E - 04	1.0
AM 243	4.4E + 02	5.2E + 02	0.8	AM 243	3.6E + 00	4.5E + 00	0.8
NP 239	2.5E - 03	2.2E - 03	1.1	NP 239	3.3E - 03	2.9E - 03	1.1
PU 239	4.3E + 02	5.1E + 02	0.8	PU 239	3.6E + 00	4.3E + 00	0.8

(a) The G/D value indicates the ratio of the GENII value to the DOE value.

Exhibit I.2. External Dose Factors for Surface Soil Contamination and Water Immersion

Soil Surface (GENII)		Water Immersion (DOE)	
Radionuclide	mrem/yr per $\mu\text{Ci}/\text{m}^3$	Radionuclide	mrem/yr per $\mu\text{Ci}/\text{m}^3$
H 3	2.57E - 10	C 14	0.00E + 00
CO60	5.80E + 01	SE79	0.00E + 00
NI63	1.40E - 06	NB94	1.77E + 01
SE79	3.93E - 05	TC99	6.18E - 06
SR90	2.62E - 03	I 129	1.07E - 01
Y 90	1.46E - 01	U 234	1.86E - 03
ZR95	1.79E + 01	U 235	1.72E + 00
NB95M	1.21E + 00	TH231	1.37E - 01
NB95	1.94E + 01	PA231	3.34E - 01
NB94	3.58E + 01	AC227	1.44E - 03
TC99	3.71E - 04	FR223	5.33E - 01
RU103	1.25E + 01	RA223	1.51E + 00
PD103	2.31E - 02	NP237	2.68E - 01
RH103M	2.45E - 03	PA233	2.37E + 00
RU106	5.61E + 00	U 238	1.29E - 03
SN113	1.14E - 01	TH234	9.13E - 02
IN113M	5.66E + 00	PA234	2.21E + 01
SB125	1.14E + 01	AM241	2.33E - 01
C 14	5.51E - 05		
TE125M	6.47E - 02		
SN126	3.83E - 01		
SB126M	4.03E - 01		
SB126	6.79E + 01		
I 129	4.08E - 02		
CS134	4.00E + 01		
CS135	1.07E - 04		
CS137	1.39E + 01		
CE144	2.28E - 01		
PR144M	3.93E - 02		
PR144	1.03E + 00		
EU152	2.77E + 01		
EU154	2.87E + 01		
EU155	6.62E - 01		

WHC-SD-WM-EE-004, Rev.1
Exhibit I.2. (contd)

Soil Surface (GENII)		Water Immersion (DOE)	
Radionuclide	mrem/yr per $\mu\text{Ci}/\text{m}^3$	Radionuclide	mrem/yr per $\mu\text{Ci}/\text{m}^3$
TH230	3.01E - 03		
RA226	6.72E - 02		
RN222	4.32E + 01		
PB210	7.66E - 03		
BI210	2.10E - 02		
PO210	2.05E - 04		
U 234	1.39E - 03		
U 235	1.76E + 00		
TH231	1.08E - 01		
PA231	6.87E - 01		
AC227	1.89E - 03		
TH227	2.02E + 00		
FR223	7.19E - 01		
RA223	6.13E + 00		
NP237	2.16E - 01		
PA233	5.19E + 00		
U 238	6.32E - 04		
TH234	4.79E - 01		
PA234	4.67E + 01		
PU242	3.83E - 04		
NP238	1.36E + 01		
PU238	4.62E - 04		
CM244	3.73E - 04		
PU244	2.72E - 04		
U 240	8.94E + 00		
PU240	4.59E - 04		
PU241	8.55E - 10		
AM241	1.05E - 01		
CM243	2.16E + 00		
PU243	2.43E - 01		
AM243	3.85E - 01		
NP239	2.96E + 00		
PU239	1.02E - 03		

Exhibit I.3. Concentration Ratios^(a) and Transfer Factors^(b) used in this PA

Element	Number	Leafy Vegetable	Other Vegetable	Fruit --	Grain --	Beef day/kg	Poultry day/kg	Milk day/L	Egg day/kg
H	1	--	--	--	--	--	--	--	--
BE	4	1.0E - 2	1.5E - 3	1.5E - 3	1.5E - 3	1.0E - 3	4.0E - 1	9.0E - 7	2.0E - 2
C	6	--	0.7	0.7	0.7	--	--	--	--
N	7	3.0E + 1	3.0E + 1	3.0E + 1	3.0E + 1	7.5E - 2	1.0E - 1	2.5E - 2	8.0E - 1
F	9	6.0E - 2	6.0E - 3	6.0E - 3	6.0E - 3	1.5E - 1	1.0E - 2	1.0E - 3	2.0E + 0
NA	11	7.5E - 2	5.5E - 2	5.5E - 2	5.5E - 2	5.5E - 2	1.0E - 2	3.5E - 2	2.0E - 1
MG	12	1.0E + 0	5.5E - 1	5.5E - 1	5.5E - 1	5.0E - 3	3.0E - 2	4.0E - 3	1.6E + 0
SI	14	3.5E - 1	7.0E - 2	7.0E - 2	7.0E - 2	4.0E - 5	2.0E - 1	2.0E - 5	8.0E - 1
P	15	3.5E + 0	3.5E + 0	3.5E + 0	3.5E + 0	5.5E - 2	1.9E - 1	1.5E - 2	1.0E + 1
S	16	1.5E + 0	1.5E + 0	1.5E + 0	1.5E + 0	1.0E - 1	9.E - 1	1.5E - 2	7.0E + 0
CL	17	7.0E + 1	7.0E + 1	7.0E + 1	7.0E + 1	8.0E - 2	3.0E - 2	1.5E - 2	2.0E + 0
AR	18	--	--	--	--	--	--	--	--
K	19	1.0E + 0	5.5E - 1	5.5E - 1	5.5E - 1	2.0E - 2	4.0E - 1	7.0E - 3	7.0E - 1
CA	20	3.5E + 0	3.5E - 1	3.5E - 1	3.5E - 1	7.0E - 4	4.4E - 2	1.0E - 2	4.4E - 1
SC	21	6.0E - 3	1.0E - 3	1.0E - 3	1.0E - 3	1.5E - 2	4.0E - 3	5.0E - 6	3.0E - 3
CR	24	7.5E - 3	4.5E - 3	4.5E - 3	4.5E - 3	5.5E - 3	2.0E - 1	1.5E - 3	8.0E - 1
MN	25	5.6E - 1	1.5E - 1	5.0E - 2	2.9E - 1	4.0E - 4	5.0E - 2	3.5E - 4	6.5E - 2
FE	26	4.0E - 3	1.0E - 3	1.0E - 3	1.0E - 3	2.0E - 2	1.5E + 0	2.5E - 4	1.3E + 0
CO	27	8.1E - 2	4.0E - 2	7.0E - 3	3.7E - 3	2.0E - 2	5.0E - 1	2.0E - 3	1.0E - 1
NI	28	2.8E - 1	6.0E - 2	6.0E - 2	3.0E - 2	6.0E - 3	1.0E - 3	1.0E - 3	1.0E - 1
CU	29	4.0E - 1	2.5E - 1	2.5E - 1	2.5E - 1	1.0E - 2	5.1E - 1	1.5E - 3	4.9E - 1
ZN	30	1.4E + 0	5.9E - 1	9.0E - 1	1.3E + 0	1.0E - 1	6.5E + 0	1.0E - 2	2.6E + 0
GA	31	4.0E - 3	4.0E - 4	4.0E - 4	4.0E - 4	5.0E - 4	3.0E - 1	5.0E - 5	8.0E - 1
AS	33	4.0E - 2	6.0E - 3	6.0E - 3	6.0E - 3	2.0E - 3	8.3E - 1	6.0E - 5	8.0E - 1
SF	34	2.5E - 2	2.5E - 2	2.5E - 2	2.5E - 2	1.5E - 2	8.5E + 0	4.0E - 3	9.3E + 0
BR	35	1.5E + 0	1.5E + 0	1.5E + 0	1.5E + 0	2.5E - 2	4.0E - 3	2.0E - 2	1.6E + 0
KR	36	--	--	--	--	--	--	--	--
RB	37	1.5E - 1	7.0E - 2	7.0E - 2	7.0E - 2	1.5E - 2	2.0E + 0	1.0E - 2	3.0E + 0
SR	38	1.6E + 0	8.1E - 1	1.7E - 1	1.3E - 1	3.0E - 4	3.5E - 2	1.5E - 3	3.0E - 1
Y	39	1.5E - 2	6.0E - 3	6.0E - 3	6.0E - 3	3.0E - 4	1.0E - 2	2.0E - 5	2.0E - 3
ZR	40	2.0E - 3	5.0E - 4	5.0E - 4	5.0E - 4	5.5E - 3	6.4E - 5	3.0E - 5	1.9E - 4
NB	41	2.0E - 2	5.0E - 3	5.0E - 3	5.0E - 3	2.5E - 1	3.1E - 4	2.0E - 2	1.3E - 3
MO	42	2.5E - 1	6.0E - 2	6.0E - 2	6.0E - 2	6.0E - 3	1.9E - 1	1.5E - 3	7.8E - 1
TC	43	4.4E + 1	1.1E + 0	1.5E + 0	7.3E - 1	8.5E - 3	3.0E - 2	1.0E - 2	3.0E + 0
RU	44	5.2E - 1	2.0E - 2	2.0E - 2	5.0E - 3	2.0E - 3	7.0E - 3	6.0E - 7	6.0E - 3
RH	45	1.5E - 1	4.0E - 2	4.0E - 2	4.0E - 2	2.0E - 3	5.0E - 1	1.0E - 2	1.0E - 1
PD	46	1.5E - 1	4.0E - 2	4.0E - 2	4.0E - 2	4.0E - 3	3.0E - 4	1.0E - 2	4.0E - 3

WHC-SD-WM-EE-004, Rev.1
Exhibit I.3. (contd)

Element	Number	Leafy Vegetable	Other Vegetable	Fruit --	Grain --	Beef day/kg	Poultry day/kg	Milk day/L	Egg day/kg
AG	47	2.7E - 4	1.3E - 3	8.0E - 4	1.0E - 1	3.0E - 3	5.0E - 1	2.0E - 2	5.0E - 1
CD	48	5.5E - 1	1.5E - 1	1.5E - 1	1.5E - 1	5.5E - 4	8.4E - 1	1.0E - 3	1.0E - 1
IN	49	4.0E - 3	4.0E - 4	4.0E - 4	4.0E - 4	8.0E - 3	3.0E - 1	1.0E - 4	8.0E - 1
SN	50	3.0E - 2	6.0E - 3	6.0E - 3	6.0E - 3	8.0E - 2	2.0E - 1	1.0E - 3	8.0E - 1
SB	51	1.3E - 4	5.6E - 4	8.0E - 5	3.0E - 2	1.0E - 3	6.0E - 3	1.0E - 4	7.0E - 2
TE	52	2.5E - 2	4.0E - 3	4.0E - 3	4.0E - 3	1.5E - 2	8.5E - 2	2.0E - 4	5.2E + 0
I	53	3.4E - 3	5.0E - 2	5.0E - 2	5.0E - 2	7.0E - 3	1.8E - 2	1.0E - 2	2.8E + 0
XE	54	--	--	--	--	--	--	--	--
CS	55	1.3E - 1	4.9E - 2	2.2E - 1	2.6E - 2	2.0E - 2	4.4E + 0	7.0E - 3	4.9E - 1
BA	56	1.5E - 1	1.5E - 2	1.5E - 2	1.5E - 2	1.5E - 4	8.1E - 4	3.5E - 4	1.5E + 0
LA	57	5.7E - 4	6.4E - 4	4.0E - 3	4.0E - 3	3.0E - 4	1.0E - 1	2.0E - 5	9.0E - 3
CE	58	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	7.5E - 4	1.0E - 2	2.0E - 5	5.0E - 3
PR	59	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	3.0E - 4	3.0E - 2	2.0E - 5	5.0E - 3
ND	60	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	3.0E - 4	4.0E - 3	2.0E - 5	2.0E - 4
PM	61	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	5.0E - 3	2.0E - 3	2.0E - 5	2.0E - 2
SM	62	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	5.0E - 3	4.0E - 3	2.0E - 5	7.0E - 3
EU	63	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	5.0E - 3	4.0E - 3	2.0E - 5	7.0E - 3
GD	64	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	3.5E - 3	4.0E - 3	2.0E - 5	7.0E - 3
TB	65	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	4.5E - 3	4.0E - 3	2.0E - 5	7.0E - 3
DY	66	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	5.5E - 3	4.0E - 3	2.0E - 5	7.0E - 3
HO	67	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	4.5E - 3	4.0E - 3	2.0E - 5	7.0E - 3
ER	68	1.0E - 2	4.0E - 3	4.0E - 3	4.0E - 3	4.0E - 3	4.0E - 3	2.0E - 5	7.0E - 3
HF	72	3.5E - 3	8.5E - 4	8.5E - 4	8.5E - 4	1.0E - 3	6.0E - 5	5.0E - 6	2.0E - 4
TA	73	1.0E - 2	2.5E - 3	2.5E - 3	2.5E - 3	6.0E - 4	3.0E - 4	3.0E - 6	1.0E - 3
W	74	4.5E - 2	1.0E - 2	1.0E - 2	1.0E - 2	4.5E - 2	2.0E - 1	3.0E - 4	8.0E - 1
RE	75	1.5E + 0	3.5E - 1	3.5E - 1	3.5E - 1	8.0E - 3	4.0E - 2	1.5E - 3	4.0E - 1
OS	76	1.5E - 2	3.5E - 3	3.5E - 3	3.5E - 3	4.0E - 1	1.0E - 1	5.0E - 3	9.0E - 2
IR	77	5.5E - 2	1.5E - 2	1.5E - 2	1.5E - 2	1.5E - 3	5.0E - 1	2.0E - 6	1.0E - 1
AL	79	4.0E - 1	1.0E - 1	1.0E - 1	1.0E - 1	8.0E - 3	5.0E - 1	5.5E - 6	5.0E - 1
HG	80	9.0E - 1	2.0E - 1	2.0E - 1	2.0E - 1	2.5E - 1	1.1E - 2	4.5E - 4	2.0E - 1
TL	81	4.0E - 3	4.0E - 4	4.0E - 4	4.0E - 4	4.0E - 2	3.0E - 1	2.0E - 3	8.0E - 1
PB	82	5.8E - 3	3.2E - 3	9.0E - 3	4.7E - 3	3.0E - 4	2.0E - 1	2.5E - 4	8.0E - 1
BI	83	3.5E - 2	5.0E - 3	5.0E - 3	5.0E - 3	4.0E - 4	1.0E - 1	5.0E - 4	8.0E - 1
PO	84	2.5E - 3	9.0E - 3	4.0E - 4	4.0E - 4	3.0E - 4	9.0E - 1	3.5E - 4	7.0E + 0
RN	86	--	--	--	--	--	--	--	--
RA	88	7.5E - 2	3.2E - 3	6.1E - 3	1.2E - 3	2.5E - 4	3.0E - 2	4.5E - 4	2.0E - 5
AC	89	3.5E - 3	3.5E - 4	3.5E - 4	3.5E - 4	2.5E - 5	4.0E - 3	2.0E - 5	2.0E - 3
TH	90	6.6E - 3	1.2E - 4	8.5E - 5	3.4E - 5	6.0E - 6	4.0E - 3	5.0E - 6	2.0E - 3
PA	91	2.5E - 3	2.5E - 4	2.5E - 4	2.5E - 4	1.0E - 5	4.0E - 3	5.0E - 6	2.0E - 3

WHC-SD-WM-EE-004, Rev.1
Exhibit I.3. (contd)

Element	Number	Leafy Vegetable	Other Vegetable	Fruit --	Grain --	Beef day/kg	Poultry day/kg	Milk day/L	Egg day/kg
U	92	1.7E - 2	1.4E - 2	4.0E - 3	1.3E - 3	2.0E - 4	1.2E + 0	6.0E - 4	9.9E - 1
NP	93	1.3E - 2	9.4E - 3	1.0E - 2	2.7E - 3	5.5E - 5	4.0E - 3	5.0E - 6	2.0E - 3
PU	94	3.9E - 4	2.0E - 4	4.5E - 5	2.6E - 5	5.0E - 7	1.5E - 4	1.0E - 7	8.0E - 3
AM	95	5.8E - 4	4.1E - 4	2.5E - 4	5.9E - 5	3.5E - 6	2.0E - 4	4.0E - 7	9.0E - 3
CM	96	3.0E - 4	2.4E - 4	1.5E - 5	2.1E - 5	3.5E - 6	4.0E - 3	2.0E - 5	2.0E - 3
CF	98	1.0E - 2	1.0E - 2	1.0E - 2	1.0E - 2	5.0E - 3	4.0E - 3	7.5E - 7	2.0E - 3

- (a) Concentration ratios for terrestrial foods are pCi/g (dry weight) of edible portions of plants per pCi/g (dry weight) of soil.
(b) Transfer factors for animal products are Ci/kg of edible flesh and eggs or Ci/L milk per Ci/day intake.

Exhibit I.4. Freshwater Fish Bioaccumulation Factors used with the GENII Code

<u>Element</u>	<u>pCi/kg Fish per pCi/L Water</u>
AC	330.0
AM	100.0
C	9000.0
I	50.0
NP	2500.0
NB	100.0
PA	30.0
RA	50.0
SE	1000.0
TH	100.0
TC	15.0
U	50.0

Exhibit I.5. Default Parameters for the Driller Scenario

GR_PA/GENII Default Parameters (9/92-sfs) Driller

Inventory Parameters

0.037, 3.7E4, 3.7E7, 3.7E10, 1.0	NVU	Source input conversion
10, 0.15, 224.0	SVU	Soil source conversion

Environmental Parameters

0.008	ABSHUM	Absolute humidity (kg/m ³)
2	PRCNTI	Air dispersion conserv. flag
0.001	DPVRES	Deposition vel./resuspension
1.0E-9	LEAFRS	Leaf resuspension factor
2.0, 2.0, 3.0, 0.8, 0.8, 0.8, 1.0, 0.8, 1.0, 1.5	BIOMAS,	BIOMA2, Biomass (kg/m ²)
0.25	DEPFR2	Interception frac./irrigate
15.0	SURCM	Depth of surface soil (cm)
224.0	SLDN	Surface soil density (kg/m ²)
1.5E3	SSLDN	Soil density (kg/m ³)
True	HARVST	Harvest removal considered?
1.37	SOLING	Soil ingested (mg/da) *
14.0	WTIM	Weathering time (da)
1.0, 0.1, 0.1, 0.1	TRANS	Translocation, plants
0.1, 0.1, 0.1, 0.1, 1.0, 1.0	TRANSA	Translocation, animal food
68.0, 0.12, 55.0, 0.12, 68.0, 55.0	CONSUM	Animal Consumption (kg/da)
50.0, 0.3, 60., 0.3	DWATER	Animal drinking water (L/da)
0.0, 0.8, 1.0, 0.8	FRACUT	Acute fresh forage by season
0.2, 0.3, 0.5, 1.0	SHORWI	Shore width factors
0.02	INGWAT	Swim water ingested (L/hr)
25295.0	TCWS	H2O/sed. transfer (L/m ² /yr)
0.4, 5.0, 4.0	YELDBT	BIOT: Veg. prod. (kg/m ² /yr)
9.41E-4, 2*7.48E-4	TOTEXC	BIOT: Excavation (m ² /m ³ -yr)

WHC-SD-WM-EE-004, Rev.1
Exhibit I.5. (contd)

GR_PA/GENII Default Parameters (9/92-sfs) Driller		
1.0, 0.81, 0.19, 0.02, 0.008, 0.002, 1.0, 0.9, 0.096, 0.006, 0.0005, 0.0005, 1.0, 0.9, 0.096, 0.006, 0.0005, 0.0005	EXCAV	BIOT: Frac. soil brought to the surface from within the waste by animal excavation
270.0	RINH	Chronic breathing (cm ³ /sec)
330.0	RINHA	Acute breathing (cm ³ /sec)
10	NDIST	Number of distances
805.0, 2414.0, 4023.0, 5632.0, 7241.0, 12068.0, 24135.0, 40255.0, 56315.0, 72405.0	X	JF/chi/Q/pop grid dist. (m)
0.1, 0.25, 6*0.18, 2*0.2	DRYFAC, DRYFA2	dry/wet ratio
<u>Metabolic Parameters</u>		
0.5, 50.0, 500.0	XDIV	
0.5, 0.5, 0.95, 0.05, 0.8, 0.0, 0.0, 0.2, 0.0, 0.1, 0.9, 0.5, 0.5, 0.15, 0.4, 0.4, 0.05, 0.0, 0.01, 0.99, 0.01, 0.99, 0.05, 0.4, 0.4, 0.135, 0.015	ADJ	
<u>Dose Parameters</u>		
0.25, 0.15, 0.12, 0.12, 0.03, 0.03, 5*0.06	WT	Weighting factors
2.0	SI2I	Semi-infinite/inf

Exhibit I.6. Default Parameters for the Post-Driller, Irrigated Farm, and River Scenarios

GR_PA/GENII Default Parameter Values (10/92-sfs) PD,IF,RV

<u>Inventory Parameters</u>		
0.037, 3.7E4, 3.7E7, 3.7E10, 1.0	NVU	Source input conversion
1.0, 0.15, 224.0	SVU	Soil source conversion
<u>Environmental Parameters</u>		
0.008	ABSHUM	Absolute humidity (kg/m ³)
2	PRCNTI	Air dispersion conserv. flag
0.001	DPVRES	Deposition vel./resuspension
1.0E-9	LEAFRS	Leaf resuspension factor
2.0, 2.0, 3.0, 0.8, 0.8, 0.8, 1.0, 0.8, 1.0, 1.5	BIOMAS	BIOMA2 Biomass (kg/m ²)
0.25	DEPFR2	Interception frac./irrigate
15.0	SURCM	Depth of surface soil (cm)
224.0	SLDN	Surface soil density (kg/m ²)
1.5E3	SSLDN	Soil density (kg/m ³)
True	HARVST	Harvest removal considered?
100.0	SOLING	Soil ingested (mg/da) *
14.0	WTIM	Weathering time (da)
1.0, 0.1, 0.1, 0.1	TRANS	Translocation, plants
0.1, 0.1, 0.1, 0.1, 1.0, 1.0	TRANSA	Translocation, animal food
68.0, 0.12, 55.0, 0.12, 68.0, 55.0	CONSUM	Animal Consumption (kg/da)
50.0, 0.3, 60., 0.3	DWATER	Animal drinking water (L/da)
0.0, 0.8, 1.0, 0.8	FRACUT	Acute fresh forage by season
0.2, 0.3, 0.5, 1.0	SHORWI	Shore width factors
0.02	INGWAT	Swim water ingested (L/hr)
25295.0	TCWS	H2O/sed. transfer (L/m ² /yr)
0.4, 5.0, 4.0	YELDBT	BIOT: Veg. prod. (kg/m ² /yr)
9.41E-4, 2*7.48E-4	TOTEXC	BIOT: Excavation (m ² /m ³ -yr)

WHC-SD-WM-EE-004, Rev.1
Exhibit I.6. (contd)

GR_PA/GENII Default Parameter Values (10/92-sfs) PD,IF,RV

1.0, 0.81, 0.19, 0.02, 0.008, 0.002, 1.0, 0.9, 0.096, 0.006, 0.0005, 0.0005, 1.0, 0.9, 0.096, 0.006, 0.0005, 0.0005	EXCAV	BIOT: Frac. soil brought to surface from within the waste by animal excavation
270.0	RINH	Chronic breathing (cm ³ /sec)
330.0	RINHA	Acute breathing (cm ³ /sec)
10	NDIST	Number of distances
805.0, 2414.0, 4023.0, 5632.0, 7241.0, 12068.0, 24135.0, 40255.0, 56315.0, 72405.0	X	JF/chi/Q/pop grid dist. (m)
0.1, 0.25, 6*0.18, 2*0.2	DRYFAC, DRYFA2	dry/wet ratio
<u>Metabolic Parameters</u>		
0.5, 50.0, 500.0	XDIV	
0.5, 0.5, 0.95, 0.05, 0.8, 0.0, 0.0, 0.2, 0.0, 0.1, 0.9, 0.5, 0.5, 0.15, 0.4, 0.4, 0.05, 0.0, 0.01, 0.99, 0.01, 0.99, 0.05, 0.4, 0.4, 0.135, 0.015	ADJ	
<u>Dose Parameters</u>		
0.25, 0.15, 0.12, 0.12, 0.03, 0.03, 5*0.06	WT	Weighting factors
2.0	SI2I	Semi-infinite/inf

References

- American Society of Mechanical Engineers (ASME). 1986. *Quality Assurance Program Requirements for Nuclear Facilities*. ANSI/ASME NQA-1, ASME, New York, New York.
- International Commission on Radiological Protection (ICRP). 1975. *Report on the Task Group on Reference Man*. ICRP Publication 23, Pergamon Press, New York.
- International Commission on Radiological Protection (ICRP). 1977. *Recommendations of the International Commission on Radiological Protection*. ICRP Publication 26, Pergamon Press, New York.
- International Commission on Radiological Protection (ICRP). 1979-1988. *Limits for Intakes of Radionuclides by Workers*. ICRP Publication 30, Parts 1-4 (and supplements), Vol. 2 (No. 3/4), Vol. 4 (No. 3/4), Vol. 6 No. 2/3), Vol. 8 (No. 4), and Vol. 19 (No.4), Pergamon Press, Elmsford, New York.
- International Commission on Radiological Protection (ICRP). 1986. *The Metabolism of Plutonium and Related Elements*. ICRP Publication 48, Vol. 16 (No. 2/3), Pergamon Press, New York.
- International Union of Radioecologists (IUR). 1989. *Sixth Report of the Working Group on Soil-to-Plant Transfer Factors*. RIVM, Bilthoven, The Netherlands.
- Kennedy, W. E., Jr. and D. L. Streng. 1992. *Residual Radioactive Contamination from Decommissioning: Volume 1, Technical Basis for Translating Contamination Levels to Annual Effective Dose Equivalent*. NUREG/CR-5512, Pacific Northwest Laboratory, Richland, Washington.
- Leigh, C. D., B. M. Thompson, J. E. Campbell, D. E. Longsine, R. A. Kennedy, and B. A. Napier. 1992. *User's Guide for GENII-S: A Code for Statistical and Deterministic Simulations of Radiation Doses to Humans from Radionuclides in the Environment*. SAND91-0561A, Sandia National Laboratories, Albuquerque, New Mexico.
- Napier, B. A., R. A. Peloquin, D. L. Streng, J. V. Ramsdell. 1988. *GENII - The Hanford Environmental Radiation Dosimetry Software System*. Vols. 1, 2, and 3. Pacific Northwest Laboratory, Richland, Washington.
- Snyder, S. F., W. T. Farris, B. A. Napier, T. A. Ikenberry, R. O. Gilbert. 1994. *Parameters Used in the Environmental Pathways and Radiological Dose Modules (DESCARTES, CIDER, and CRD codes) of the Hanford Environmental Dose Reconstruction Integrated Codes (HEDRIC)*. PNWD-2023 HEDR Rev. 1, Battelle Pacific Northwest Laboratories, Richland, Washington.

U.S. Department of Energy (DOE). 1988a. *External Dose-Rate Conversion Factors for Calculation of Dose to the Public*. DOE/EH-0070, U.S. DOE, Assistant Secretary for Environment, Safety and Health, Washington, D.C.

U.S. Department of Energy (DOE). 1988b. *Internal Dose Conversion Factors for Calculation of Dose to the Public*. DOE/EH-0071, U.S. DOE, Assistant Secretary for Environment, Safety and Health, Washington, D.C.

Appendix J

Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford^(a)

-
- (a) This appendix is a reproduction of PNL-8813 (M. L. Rockhold, M. J. Fayer, and P. R. Heller. 1993. *Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford*. PNL-8813, Pacific Northwest Laboratory, Richland, Washington.

PHYSICAL AND HYDRAULIC PROPERTIES OF SEDIMENTS
AND ENGINEERED MATERIALS ASSOCIATED WITH GROUTED
DOUBLE-SHELL TANK WASTE DISPOSAL AT HANFORD

M. L. Rockhold
M. J. Fayer
P. R. Heller

September 1993

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

SUMMARY

Numerical models are used to predict the fate of contaminants in the environment for durations of 10,000 years and more. At the Hanford Site, these models are being used to evaluate the potential health effects and environmental impacts associated with the disposal of double-shell tank waste in grouted vaults. These models require information on the properties of the earthen and manufactured materials that compose the vault system and its surroundings. This report documents the physical and hydraulic properties of the materials associated with burial of grouted double-shell tank waste at the Hanford Site.

A conceptual model of the grout site and engineered structures was used to identify those materials that are, in a first-order sense, dominant controllers of the flow and transport regime. These materials are the Hanford formation sandy sequence, Hanford formation lower gravels, Ringold Formation, backfill soil, gravel, asphalt, concrete, clay cap, and the grouted waste form itself. The published physical and hydraulic data for these materials were identified. If unpublished but available, the data were included in this report. If data were non-existent, estimates were provided along with the rationale for the estimates.

In numerical flow and transport models, the hydraulic properties of porous media are represented by mathematical functions. For the grout performance assessment, the chosen functions were the van Genuchten water retention function and the Mualem hydraulic conductivity function. The parameters in these functions were fitted to the data provided in the Appendix or taken from other publications. For each material in the conceptual model, parameter values were assigned for use in the performance assessment models. For some materials, the number of samples allowed for calculation of means and variances of the parameters. For other materials, the parameters were determined from only one sample. Recommendations are provided for future data collection and parameter estimation. What is needed most is a program dedicated to identifying the important materials, identifying the conditions to which those materials will be subjected, and measuring the properties under

those conditions. Creating a research program now would ensure that the appropriate hydraulic models are identified and parameters for simulations are obtained in a timely fashion.

ACKNOWLEDGMENTS

This work was conducted by the Pacific Northwest Laboratory (PNL) in collaboration with Westinghouse Hanford Company (WHC) for the U. S. Department of Energy. We would like to thank Andy Felmy for estimating water activities for grout and concrete using the GMIN computer code and Charley Kincaid and Gary Streile for providing technical review comments.

CONTENTS

SUMMARY	iii
ACKNOWLEDGMENTS	v
1.0 INTRODUCTION	1.1
2.0 MATERIAL IDENTIFICATION	2.1
2.1 STRATIGRAPHIC SECTION	2.1
2.2 CONCEPTUAL MODEL	2.1
2.2.1 Hanford Formation Sandy Sequence	2.1
2.2.2 Hanford Formation Lower Gravels	2.4
2.2.3 Ringold Formation	2.5
2.2.4 Backfill Soil	2.5
2.2.5 Gravel	2.5
2.2.6 Clay	2.6
2.2.7 Asphalt	2.6
2.2.8 Concrete	2.6
2.2.9 Grout	2.7
3.0 MEASUREMENTS AND ESTIMATES OF PROPERTIES	3.1
3.1 METHODS	3.1
3.1.1 Particle Size Distribution	3.1
3.1.2 Particle Density	3.2

3.1.3	Bulk Density	3.2
3.1.4	Total Porosity	3.2
3.1.5	Water Retention	3.2
3.1.6	Saturated Hydraulic Conductivity	3.9
3.2	RESULTS	3.11
3.2.1	Hanford Formation Sandy Sequence	3.11
3.2.2	Hanford Formation Lower Gravels	3.12
3.2.3	Ringold Formation	3.12
3.2.4	Backfill Soil	3.12
3.2.5	Gravel	3.13
3.2.6	Clay	3.13
3.2.7	Asphalt	3.14
3.2.8	Concrete	3.15
3.2.9	Grout	3.15
4.0	HYDRAULIC PARAMETERS	4.1
4.1	HYDRAULIC FUNCTIONS	4.1
4.2	PARAMETER ESTIMATION PROCEDURE	4.2
4.3	CORRECTIONS FOR GRAVEL CONTENT	4.3
4.4	PARAMETER SUMMARY	4.4
5.0	DISCUSSION	5.1
5.1	METHODS	5.1

5.2	BULK DENSITY	5.3
5.3	HYDRAULIC CONDUCTIVITY	5.3
5.4	GRAVEL CONTENT	5.4
5.5	SPATIAL VARIABILITY	5.5
5.6	HYSTERESIS	5.6
5.7	ANISOTROPY	5.6
5.8	TEMPERATURE AND SOLUTE EFFECTS	5.7
5.9	GEOCHEMISTRY	5.9
5.10	DEGRADATION	5.10
6.0	REFERENCES	6.1
	APPENDIX - PHYSICAL AND HYDRAULIC PROPERTY DATA	A.1

FIGURES

2.1	Relative Locations of the Grout Treatment Facility and Characterization Wells Around the 200 East Area	2.2
2.2	Sediment Stratigraphy in the Vicinity of the Grout Site	2.3
2.3	Conceptual Model of Vertical Cross Section Through a Grout Vault and Underlying Sediment Stratigraphy	2.4
3.1	Schematic of Apparatus Used to Measure Water Retention by the Hanging Water Column Method	3.5
3.2	Schematic of Apparatus Used to Measure Water Retention by the Pressure-Plate Method	3.6
3.3	Schematic of Apparatus Used to Measure Saturated Hydraulic Conductivity by the Falling-Head Method	3.10
4.1	Average Water Retention and Hydraulic Conductivity Curves	4.6
A.1	Water Retention and Hydraulic Conductivity Data and Curves for Samples 5A, 5B, 19A, and 19B from Well No. 299-E25-234	A.16
A.2	Water Retention and Hydraulic Conductivity Data and Curves for Samples 25A, 25B, 25C, and 25D from Well No. 299-E25-234	A.17
A.3	Water Retention and Hydraulic Conductivity Data and Curves for Samples 29A, 29B, 37A, and 37B from Well No. 299-E25-234	A.18
A.4	Water Retention and Hydraulic Conductivity Data and Curves for Samples 46A, 46B, 54A, and 54B from Well No. 299-E25-234	A.19
A.5	Water Retention and Hydraulic Conductivity Data and Curves for Samples 69A, 69B, 83A, and 83B from Well No. 299-E25-234	A.20
A.6	Water Retention and Hydraulic Conductivity Data and Curves for Samples 99A, 99B, 110A, and 110B from Well No. 299-E25-234	A.21

A.7	Water Retention and Hydraulic Conductivity Data and Curves for Samples 117A, 117B, 126A, and 126B from Well No. 299-E25-234	A.22
A.8	Water Retention and Hydraulic Conductivity Data and Curves for Samples 133A and 133B from Well No. 299-E25-234	A.23
A.9	Water Retention and Hydraulic Conductivity Data and Curves for Backfill Soil	A.24
A.10	Water Retention and Hydraulic Conductivity Data and Curves for Gravel	A.24
A.11	Water Retention and Hydraulic Conductivity Data and Curves for RCRA Clay Cap	A.25
A.12	Water Retention and Hydraulic Conductivity Data and Curves for Concrete Samples CL-40A, CL-40B, CL-40C, and CL-40D	A.26
A.13	Water Retention and Hydraulic Conductivity Data and Curves for Concrete Samples CL-40E and CL-40F	A.27
A.14	Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Samples A26, A38, A73, and B06	A.28
A.15	Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Samples B33, B52, C16, and C48	A.29
A.16	Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Sample C82	A.30

TABLES

4.1 Average Water Retention Parameters and Vertical Saturated Hydraulic Conductivity Values Used for Grout Vadose Zone Flow and Transport Modeling	4.5
A.1 Particle-Size Distribution Data for Sediment Samples from Well No. 299-E25-234	A.1
A.2 Bulk and Particle Density Data for Samples from Well No. 299-E25-234	A.5
A.3 Particle Size Distribution and Water Retention Data for Backfill Soil	A.6
A.4 Water Retention Data for Gravel	A.6
A.5 Water Retention Data for Clay	A.7
A.6 Bulk and Particle Density and Saturated Hydraulic Conductivity Data for Concrete	A.7
A.7 Water Retention Data for Concrete	A.8
A.8 Bulk and Particle Density and Saturated Hydraulic Conductivity Data for DSSF Grout Samples from the 14 November 1988 Adiabatic Pilot-Scale Test	A.9
A.9 Water Retention Data for DSSF Grout	A.10
A.10 Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Sandy Sequence of the Hanford Formation	A.12
A.11 Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Upper and Lower Gravel Units of the Hanford Formation	A.14
A.12 Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Ringold Formation	A.14
A.13 Water Retention Parameters and Saturated Hydraulic Conductivity Data for Concrete	A.15

A.14 Water Retention Parameters and Saturated Hydraulic Conductivity Data for DSSF Grout	A.15
---	------

1.0 INTRODUCTION

At the Hanford Site in south-central Washington State, numerical models are being used in a performance assessment to evaluate the potential health effects and environmental impacts associated with the disposal of double-shell tank waste in grouted vaults. These models require information on the properties of the earthen and manufactured materials that compose the vault system and its surroundings. The data and parameter estimates contained in this report support the unsaturated flow and contaminant transport modeling studies and sensitivity analyses for the Hanford Grout Technology Program (HGTP) Performance Assessment (PA) Task. This work was conducted for the U.S. Department of Energy by Pacific Northwest Laboratory (PNL)^(a) in collaboration with Westinghouse Hanford Company (WHC).

The two purposes of this report are to identify the significant materials and sediments that govern the movement of water and contaminants in and around the proposed Grout Treatment Facility (GTF) and to estimate the parameters that describe the hydraulic properties of those materials. The data supporting the parameter estimate came from three sources: published reports, laboratory record books, or estimates. The published data and parameters are referenced in this report. All unpublished data and estimated parameters are included in this report as an appendix.

This report is organized as follows. Section 2 describes the grout site and sediment sample locations at Hanford, the general sediment stratigraphy at the grout site, and the operative conceptual model of a buried grout vault. Section 3 describes the methods used to determine physical and hydraulic properties and identifies the data sources (if the data are not reported here). Section 4 describes the parameter estimation procedures and identifies the average hydraulic parameters to be used in the grout PA simulations. Section 5 discusses the data and assumptions to be used for

(a) Operated for the U.S. Department of Energy by Battelle Memorial Institute under contract DE-AC06-76RLO 1830.

unsaturated flow modeling. The Appendix contains the physical and hydraulic property data that have not been reported elsewhere, as well as the hydraulic parameters for all samples used to describe the average hydraulic properties of each material.

2.0 MATERIAL IDENTIFICATION

The purpose of this section is to identify the sediments and engineered materials composing the grout disposal system that are important to the system's performance regarding the release of contaminants. Figure 2.1 shows the position of the GTF within the 200 East Area of the Hanford Site. The hydrogeology of the 200 East Area is summarized by Cushing (1992).

2.1 STRATIGRAPHIC SECTION

The available well logs and sediment sample analyses were reviewed to identify the dominant sediment features at the GTF. Figure 2.1 shows the locations of these wells and sediment samples relative to the GTF. Figure 2.2 shows the stratigraphy at the GTF. Based on that information, a general stratigraphy of the GTF was developed. Underlying the Ringold Formation (Figure 2.2) is the Elephant Mountain Member. The permeability of this basalt member is much lower than that for the overlying sediments and the member was therefore considered to be impermeable. For that reason, the Elephant Mountain Member was not considered part of the hydrologic system at the GTF and was not evaluated for this report.

2.2 CONCEPTUAL MODEL

Figure 2.3 shows the current conceptual model of a grout vault at the GTF. Each material type is briefly described below.

2.2.1 Hanford Formation Sandy Sequence

The sandy sequence of the Hanford formation is a coarse-to-fine-grained sand unit that averages 60-m thick in the 200 East Area. Information representing the sandy sequence was derived from 28 samples collected from well No. 299-E25-234, 5 samples from the 241 AP Tank Farm Facility, 21 samples from the U.S. Ecology site, 3 samples from the 200-BP-1 site, and 3 measurements at the bottom of the existing grout pit (Dames and Moore 1988).

FIGURE 2.1. Relative Locations of the Grout Treatment Facility and Characterization Wells Around the 200 East Area (some sample locations were identified from Connelly et al. 1992b). Sample locations are identified by closed-circle symbols.

FIGURE 2.2. Sediment Stratigraphy in the Vicinity of the Grout Site

S9305096.5

FIGURE 2.3. Conceptual Model of Vertical Cross Section Through a Grout Vault and Underlying Sediment Stratigraphy (MSL = Mean Sea Level)

2.2.2 Hanford Formation Lower Gravels

This material is a pebbly, very coarse sand-to-sandy gravel, about 10 m thick, that overlies the Ringold Formation. Information representing the lower gravels was derived from two samples that were obtained from well No. 299-E25-234, eight samples from the 200-BP-1 site, two samples from B Pond, and two samples from the U.S. Ecology site. Some of the samples were from the upper

gravel sequence of the Hanford formation, which is absent in the vicinity of the GTF. The upper and lower gravel sequences of the Hanford formation are texturally similar and more or less indistinguishable from each other except for stratigraphic position (Connelly et al. 1992a, 1992b).

2.2.3 Ringold Formation

The Ringold Formation averages 30 m thick and consists of well-rounded pebble- to cobble-size gravel with a matrix of sand, silt, and some clay. The Ringold Formation is variably indurated and consolidated, ranging from well-cemented conglomerate to open-work uncemented gravel. Information representing the Ringold Formation was obtained from four samples from B Pond and one sample from the U.S. Ecology site. No samples of the Ringold Formation beneath the GTF were available.

2.2.4 Backfill Soil

During construction, the Hanford formation sandy sequence will be excavated to depths of 20 m. This material will be stockpiled and then used to backfill around the vaults when the vaults are completed. Because the sediments will be somewhat mixed, retaining none of the in situ layering, and because it will be compacted to specifications, the backfill material was considered to be a unique and important material.

The material used to represent the backfill soil was obtained from a stockpile of sand that was excavated during construction of the grout pit. The material was sieved so that only the <2-mm size fraction was used to determine hydraulic properties. The resulting particle size distribution was 91% sand, 3% silt, and 6% clay.

2.2.5 Gravel

Gravel will serve as the drainage layer (not shown in Figure 2.3) in the collection basin beneath the grout. Gravel will also be formed into a sloped capillary barrier above the vault, serving to

redirect downward-flowing water to the region beyond the sides of the vault where it can drain freely without impacting the vault contents. Several gravel sizes will be used as filters and drains. No samples of the actual gravel that will be used were available. As a surrogate for whatever gravel is used, a gravel sample was prepared from 0.5-in.- (1.3-cm-) diameter chipped gravel that was wet sieved through an 8-mm sieve and retained on a 3.962-mm sieve. This procedure left a clean gravel material (i.e., clean in that it was free of fine materials like sands, silts, and clays).

2.2.6 Clay

A compacted clay layer will be used to satisfy the Resource Conservation and Recovery Act (RCRA) requirement for a compacted clay cap over the disposal site. The clay layer will be sloped to divert percolating water away from the vault. The material that was used to represent the RCRA clay cap was a 1:3 mixture of bentonite and Warden silt loam. This silt loam was obtained from the McGee Ranch, which is located on the west side of the Hanford Site, adjacent to the Yakima barricade.

2.2.7 Asphalt

Asphalt will surround the grout vault and, being nearly impermeable, will serve as a barrier to water flow and contaminant diffusion. No samples of asphalt were available for testing.

2.2.8 Concrete

Concrete will be used to create a structure, or vault, into which the contaminant-grout mixture can be poured, cured, and stored. A sample of concrete was obtained by PNL in 1984 from Sandia National Laboratories, who had obtained the concrete from the U.S. Army Waterways Experiment Station. The sample was a cylinder that was 15 cm long and 7.5 cm in diameter. Six subsamples were cut from the original sample and analyzed for hydraulic properties. Because these data were readily available, they were used to represent the hydraulic properties of the concrete used at the GTF.

2.2.9 Grout

Grout is a stabilizing agent used to improve the structural properties or reduce the permeability of earthen materials. For the current grout PA, wastes from the double-shell tanks will be processed into a grout; the resulting mixture is called double-shell slurry feed (DSSF) grout.

On 14 November 1988 a pilot-scale test was conducted to determine physical and chemical characteristics of a single formulation of DSSF grout. That formulation was a blend of (by weight) 47% blast furnace slag, 47% fly ash, and 6% type I/II Portland cement (Lokken et al. 1992a). Core samples were obtained and tested to obtain physical and hydraulic data. Simulated wastes with the same formulation used for the pilot-scale test were generated for durability studies (Lokken et al. 1992b). Information from the durability studies was used to supplement data from the core samples.

3.0 MEASUREMENTS AND ESTIMATES OF PROPERTIES

Measurements of physical and hydraulic properties are needed to determine the hydraulic property parameters for the materials that comprise the conceptual model in Figure 2.3. In lieu of measurements, reasonable estimates of the properties are required. This section summarizes the methods and results.

3.1 METHODS

The methods described below were used to measure or estimate the physical and hydraulic properties reported in the Appendix and by Smoot et al. (1989).

3.1.1 Particle Size Distribution

The distribution of particle sizes is one of the basic (and commonly the only) measures of the physical properties of the sediment. Generally, the sample is sieved to remove those particles greater than 2 mm in diameter before further testing is conducted. The particles removed are categorized as gravel. The percentage of the total sample that is gravel is rarely reported although, for the sediments at the Hanford Site, the percentages can be quite high.

Ideally, the distribution of particle sizes below 2 mm in diameter is not used directly to calculate hydraulic parameters. Rather, the distribution is used to qualitatively classify sediments into categories known as textures, such as clay or sand. If other data are lacking, however, these classifications can be used to infer hydraulic properties based on the hydraulic properties of sediments with similar texture.

The two procedures used to determine particle size distribution were those of the American Society for Testing and Materials (ASTM) (1985) and Gee and Bauder (1986). Approximately 50 g

of material that passed a 2-mm sieve was used with the hydrometer method and wet sieving to measure the distribution over the full range of sizes below 2 mm.

3.1.2 Particle Density

The density of particles (ρ_s) was determined using the pycnometer method (Blake and Hartge 1986a). About 10 g of the material less than 2 mm in diameter was used. Although significant gravel percentages were measured in some sediment samples, the density of the gravel was not determined.

3.1.3 Bulk Density

The dry bulk density (ρ_b) of a porous medium is the ratio of its oven-dried mass to its total volume. The bulk densities of the materials described in this report were determined using the method outlined by Blake and Hartge (1986b).

3.1.4 Total Porosity

The total porosity (ϕ_t) of a porous material is a measure of the relative volume of pores capable of filling with water and/or air. Total porosity can be calculated from particle and bulk densities according to the equation (Hillel 1982):

$$\phi_t = 1 - \rho_b/\rho_s \quad (3.1)$$

The total porosity of all the engineered materials described in this report was determined using Equation (3.1).

3.1.5 Water Retention

Four different methods were used to determine water retention data over the full range of matric potentials from fully saturated to residual (irreducible) saturation. In all cases, the

measurements were conducted on drained or draining samples. No measurements were made as the samples were wetted, which would have documented the extent of hysteresis.

The methods used were 1) the hanging water column method (Klute 1986), 2) a column method, 3) the pressure-plate extraction method (Klute 1986), and 4) the vapor equilibrium (or thermocouple psychrometer) method (Rawlins and Campbell 1986). When possible, undisturbed samples that retained the in situ structure were obtained. Most of the samples, however, were disturbed (i.e., did not retain their in situ structure); to conduct the tests, these samples were packed to known densities. Water retention varies more between disturbed and undisturbed samples when matric potentials are near zero.

Water retention is the relationship between the water content and the matric potential of a porous medium. The total potential (h_t) of the water in a sample is commonly expressed as the sum of the individual water-potential components as follows (Hillel 1982) :

$$h_t = h_{os} + h + h_g + h_p \quad (3.2)$$

where h_{os} = osmotic potential,

h = matric potential,

h_g = gravitational potential,

h_p = pressure potential.

The osmotic potential represents the attractive forces of water to locations of higher solute concentration. The matric potential represents the capillary and adsorptive forces that attract and bind water to the soil matrix. The gravitational potential is the energy associated with the location of water in the earth's gravitational field, measured with respect to some reference level such as the soil surface or the water table. The pressure potential represents external pressure forces, such as the weight of ponded water.

The application of this total potential concept to soil water equilibrium and transport is not exact because the osmotic potential applies only to the water, and the other components apply to the soil solution (Corey and Klute 1985; Sposito 1986). It is commonly assumed, however, that the osmotic component of the total water potential has only a negligible effect on the transport of water in soil, especially considering the absence of a differentially permeable membrane in the water flow path (Taylor and Ashcroft 1972; Hillel 1982). Exceptions to the assumption of negligible osmotic potentials for grout and concrete are noted later in this report.

3.1.5.1 Hanging Water Column

Water retention was measured in the 0- to -150-cm range of matric potential using the hanging water column method. Figure 3.1 shows a typical hanging water column apparatus. The soil sample was placed on the porous plate, saturated, then allowed to drain until hydraulic equilibrium was established between the soil water and the water in the reference system. The reference elevation was the soil-plate interface. With that reference, the matric potential of the soil water at the bottom of the sample was equivalent to the negative of the distance (Z_1) between the outflow point and the plate.

Decreasing matric potentials were obtained by increasing the distance Z_1 . After equilibrium was established following a decrease in potential, outflow volumes were measured. After equilibrium was achieved following the final decrease in potential, the final volumetric water content was measured and used to calculate the water contents at the intermediate potentials. If the sample was undisturbed (i.e., not packed), the bulk density was also determined.

3.1.5.2 Column Method

A column method was used to measure retention in the matric potential range from 0 to -100 cm (or more, depending on column length) for the backfill material and the gravel. Two Plexiglass columns, composed of short lengths and taped together, were filled with one of the materials. The columns were saturated and then allowed to drain. Following the cessation of drainage, the

S9305096.3

FIGURE 3.1. Schematic of Apparatus Used to Measure Water Retention by the Hanging Water Column Method

columns were sectioned to determine water contents along their length. The matric potentials in each section were ascribed to the negative of the distance from the section midpoint to the drain, assuming the column was in equilibrium with the drain.

3.1.5.3 Pressure-Plate Extraction Method

Water retention was measured in the -310- to -15,300-cm range of matric potential using two variations of the pressure-plate extraction method. Figure 3.2 shows the typical extraction method in which multiple samples are simultaneously subjected to the same pressure force, one pressure increment at a time. The samples and porous plate were saturated, the pressure vessel sealed, the internal pressure raised to a predetermined level, and the samples allowed to equilibrate at the new pressure.

S9305096.4

FIGURE 3.2. Schematic of Apparatus Used to Measure Water Retention by the Pressure-Plate Method

After the samples equilibrated, the pressure vessel was opened and the samples were weighed to determine gravimetric water contents. These water contents were converted to volumetric values by multiplying by the bulk density of the material.

A variation of the pressure-plate extraction method, the Tempe cell, was used and allowed an individual sample to be subjected to multiple pressures before the vessel was opened. The change in weight between each step increase in pressure determined the water content after the final water content was measured.

3.1.5.4 Vapor Equilibrium Method

Water retention was measured at all matric potentials less than -15,300 cm using the vapor equilibrium method. Water retention was also measured with this method at potentials up to

-1,000 cm, although the sensitivity of this method in that potential range is not as great (e.g., relative humidity varies from approximately 1.0 at -1,000 cm to 0.989 at -15,300 cm). The matric potential of water in a porous material can be calculated from measurements of the vapor phase in equilibrium with the liquid in the pores. When the vapor phase is represented by the relative humidity (p/p^*), the total potential (assuming h_p and h_g are zero) is:

$$h_t = (RT / M) \ln (p/p^*) \quad (3.3)$$

where M = molecular weight of water ($0.01802 \text{ kg mol}^{-1}$),

R = ideal gas constant ($8.3143 \times 10^{-3} \text{ kg MPa mol}^{-1} \text{ K}^{-1}$),

T = Kelvin temperature of the liquid phase ($^{\circ}\text{C} + 273.16$),

p = water vapor pressure in equilibrium with the liquid phase,

p^* = saturated water vapor pressure at temperature T .

If the osmotic potential is negligible, the matric potential is equivalent to the total potential in Equation (3.3). When the osmotic potential is significant, the matric potential is calculated as the difference between the total and osmotic potentials. The osmotic potential of a solution (outside the porous medium) is calculated by determining the water activity (A_w) based on the total ionic concentration of the solution, and then applying an equation similar to Equation (3.3), where p/p^* and h_t are replaced with A_w and h_{os} , respectively.

The vapor equilibrium tests were conducted using a commercially available instrument (either the SC-10 or CX-1 Water Activity Meter, Decagon Devices, Inc., Pullman, WA 99163) or several saturated salt solutions with known vapor pressures. Because vapor adsorption is relatively independent of bulk density, no attempt was made to pack the samples to a specific density.

The SC-10 uses a thermocouple psychrometer to measure the wet-bulb depression in a closed chamber containing a soil sample. The CX-1 uses a cooled mirror to measure the dewpoint

temperature. The saturated salt solutions used were LiCl, MgCl₂, and Mg(NO₃)₂. These solutions yielded relative humidities (and corresponding matric potentials in MPa) of 11.3% (-300), 32.8% (-153), and 52.9% (-87.6), respectively, at a temperature of 25°C (Greenspan 1977).

The salt content of the pore water solutions of the sediments in the vicinity of the grout test facility were unknown. Murphy et al. (1991) reported ionic concentrations for six of the major surface soils at the Hanford Site. The low concentrations (e.g., for K⁺, 100 µg/g soil for two different sands) suggested that osmotic potential would not significantly affect the measurement of total potential using the vapor equilibrium method. Therefore, the matric potentials for the sediment samples were assumed to be equal to the measured total potentials.

Total pore solution concentrations of 12 ions in six samples of simulated DSSF grout ranged from 315 to 410 g/L and the solution pH values were greater than 13 (Lokken et al. 1992b). These high salt concentrations suggested that the osmotic potential of this grout was significant. Likewise, data for the aqueous phase of concrete suggested that this material could also have a significant osmotic potential (Bailey and Hampson 1982; Angus and Glasser 1985; Reardon 1990).

Osmotic potentials for the grout and concrete were calculated from solution chemistry data using the GMIN chemical equilibrium model (Felmy 1990), and Equation (3.3). The GMIN model was used to estimate the activity of water with multiple solutes in the pore waters of the materials. The mathematical algorithm in GMIN is based on a constrained minimization of the Gibbs free energy. The excess free energy in the aqueous phase (as indicated by the activity coefficient) is represented using the equations developed by Pitzer (1973; 1979), and parameters from Harvie et al. (1984) that are valid for solutions with high ionic strengths.

3.1.6 Saturated Hydraulic Conductivity

Laboratory measurements of the saturated hydraulic conductivity (K_s) of a porous medium are based on the application of the Darcy flow equation to a sample of uniform cross-sectional area. Two different methods were used to determine K_s for the materials in this study. For the majority of materials, the falling-head method was used. For the high-permeability materials such as the coarse sands and gravels, a constant head method was used. For the low-permeability materials such as the grout and concrete, a modified constant-head method was used.

3.1.6.1 Falling-Head Method

Figure 3.3 is a schematic representation of the apparatus used for measuring K_s by the falling-head method (Klute and Dirksen 1986). The calculation of K_s is as follows:

$$K_s = (aL/At)\ln(H_1/H_2) \quad (3.4)$$

where a = cross-sectional area of the standpipe,

L = length of the sample,

A = cross-sectional area of the sample,

t = time required for the head difference to decrease from H_1 to H_2 ,

H_1, H_2 = initial and final hydraulic head differences, respectively.

3.1.6.2 Constant Head Method

In the constant head method, the apparatus is similar to that in Figure 3.3. The difference is that the head at the inflow port is held constant at H_2 and the volume of outflow is measured. The calculation of K_s is as follows:

$$K_s = VL / (A t H_2) \quad (3.5)$$

FIGURE 3.3. Schematic of Apparatus Used to Measure Saturated Hydraulic Conductivity by the Falling-Head Method

where V = volume of water flowing through the sample,

L = length of sample,

A = cross-sectional area of sample,

t = time,

H_2 = constant hydraulic head difference.

For the clay, concrete, and grout samples, the K_s values were determined using the Ruska permeameter (Model No. 1013-801-00, Ruska Instrument Corp., Houston, Texas). The Ruska permeameter is a constant head device that confines small samples under relatively high pressures. The K_s value of a sample is calculated using Equation (3.5), where the hydraulic head difference (H_2) equals the difference between the applied pressure and atmospheric pressure (Klute and Dirksen 1986).

3.2 RESULTS

This section summarizes the measured and estimated hydraulic properties. If data were reported elsewhere, the reference(s) was cited.

3.2.1 Hanford Formation Sandy Sequence

The water retention and saturated hydraulic conductivity data describing the Hanford sandy sequence were reported by Smoot et al. (1989; 33 samples) and Connelly et al. (1992b; 27 samples). While most of the characterization data for well No. 299-E25-234 at the GTF were reported by Smoot et al. (1989), the particle size distributions were not included. For completeness, those data are included in this report in Table A.1 of the Appendix. All particles greater than 2 mm in diameter were included in the gravel percentage for each sample.

Smoot et al. (1989) reported bulk density values for the samples from well E25-234. Those data are included in Table A.2 of the Appendix to show how bulk density varied as a function of depth and sample size. Also contained in Table A.2 are the average particle density values determined on the less than 2-mm-diameter size fraction. These data were not reported by Smoot et al. (1989).

3.2.2 Hanford Formation Lower Gravels

The water retention and saturated hydraulic conductivity data describing the Hanford gravels were reported by Smoot et al. (1989; two samples) and Connelly et al. (1992b; 12 samples). Of the 14 samples, gravel contents were reported for 10. The gravel contents ranged from 0% to 79%, with an average of approximately 50%. Table A.1 contains the average particle size distribution and Table A.2 the bulk and particle density data for samples from well No. 299-E25-234 (Smoot et al. 1989). Connelly et al. (1992b) reported dry sieve data for 8 of the 12 samples, but did not report bulk or particle density values.

3.2.3 Ringold Formation

The water retention and saturated hydraulic conductivity data describing the Ringold Formation were reported in Connelly et al. (1992b; 5 samples). Particle size distribution and bulk and particle densities were not estimated because the hydraulic parameters were already provided.

3.2.4 Backfill Soil

The water retention properties of backfill were determined between 0 and -100 cm of matric potential using the column method with two Plexiglass columns packed to a bulk density of 1.65 g cm^{-3} . This density represented 90% of the maximum dry density (Dames and Moore 1988). The retention data from the column method were combined with pressure plate and vapor adsorption data to describe the full range of water retention. Particle size distribution and water retention data are contained in Table A.3 of the Appendix. Particle density was assumed to be 2.8 g cm^{-3} .

The saturated hydraulic conductivity was determined with the constant head method using two 30-cm-long columns with an area of 17.65 cm^2 . A 2-cm head was maintained on the surface, resulting in a head gradient of 1.067 across the columns. Four 10-s repetitions of the test on each column yielded average saturated conductivity values of 0.024 and 0.036 cm s^{-1} , for an overall

average K_s of 0.030 cm s^{-1} . The source of the retention and conductivity data for the backfill soil was PNL laboratory record book BNW 53071.

3.2.5 Gravel

The water retention properties of gravel were determined between 0 and -10 cm of matric potential using the column method with two Plexiglass columns packed to a bulk density of 1.38 g cm^{-3} . Those data were combined with a vapor adsorption datum and linear interpolation to estimate the full range of water retention. Particle density was assumed to be 2.8 g cm^{-3} . The water retention data are contained in Table A.4 of the Appendix. The only information on particle size distribution is that all particles are between 3.692 mm and 8 mm in diameter.

The saturated hydraulic conductivity was determined with the constant head method using a 10-cm-long column with an area of 17.65 cm^2 . A head gradient of 2.5 cm was maintained across the column. Five 10-second repetitions yielded a range of values from 1.77 to 1.97 cm s^{-1} and an average value of 1.85 cm s^{-1} . The K_s value (1.85 cm s^{-1}) and the experimental design may have resulted in a Reynolds number in excess of 80, which would indicate turbulence, decreased flow through the sample, and deviation from Darcy's law. Assuming that the effect of the turbulence would be to reduce flow relative to flow under laminar conditions, the actual conductivity value was probably somewhat higher than that reported. In the absence of any other data, however, these hydraulic conductivity estimates were assumed to be reasonable first approximations. The source of the retention and conductivity data for the gravel was PNL laboratory record book BNW 53071.

3.2.6 Clay

The water retention properties of the clay were determined using the pressure plate method (samples were packed to a density of 1.45 g cm^{-3} , which represented roughly 90% of the maximum

dry density as extrapolated from data in Dames and Moore [1988]) and the vapor adsorption method. Particle density was assumed to be 2.6 g cm^{-3} . The water retention data are contained in Table A.5 of the Appendix.

The saturated hydraulic conductivity was determined in triplicate using the constant head method and the Ruska permeameter. The applied pressure difference was 510 cm across a 6.45-cm-long sample with an area of 18.1 cm^2 . The tests were run for about 54 hours and outflow volumes were 8 to 10 cm^3 . The three conductivity values were 1.23×10^{-9} , 7.75×10^{-9} , and $8.26 \times 10^{-9} \text{ cm s}^{-1}$, for an average value of $9.4 \times 10^{-9} \text{ cm s}^{-1}$. After the tests, the conductivity samples remained in the sample cells for 42 days and swelled. The increase in sample length was roughly 30%. The conductivity test was performed again with a pressure difference of 1,020 cm. After about 0.4 hours, the outflow was about 2 cm^3 . The average calculated K_s value was $1.8 \times 10^{-7} \text{ cm s}^{-1}$, or approximately 20 times the original value. The source of the retention and conductivity data was PNL laboratory record book BNW 53071.

3.2.7 Asphalt

No data were initially available. Asphalt was assumed to be impermeable to liquid water; hence, hydraulic properties were assigned to satisfy that assumption yet remain compatible with properties of adjacent materials. The assigned values of saturated and residual water contents were 0.162 and $0.0 \text{ cm}^3 \text{ cm}^{-3}$, respectively. The assigned value of saturated conductivity was $10^{-20} \text{ cm s}^{-1}$. After this report was drafted, asphalt data became available. Clemmer et al. (1992) estimated that the total porosity of three samples was 3% to 4%, which was about 1/4 the assumed value of 16.2%. Based on the permeability to N_2 , the asphalt permeability to water was estimated to be $2 \times 10^{-13} \text{ cm s}^{-1}$.

3.2.8 Concrete

Bulk density, particle density, and hydraulic conductivity data are contained in Table A.6 of the Appendix. Saturated hydraulic conductivity was determined using the constant head method and the Ruska permeameter with a pressure difference of 2,068 cm across the samples. The average value, $3.88 \times 10^{-10} \text{ cm s}^{-1}$, was within the range of values reported by Whiting (1988) for seven types of concrete.

Water retention by concrete was determined using only the vapor equilibrium technique because the pressures required to remove water from this material were much greater than those that could be obtained with the other techniques. Water retention data for the concrete are reported in Table A.7 of the Appendix.

Bailey and Hampsen (1982) listed ion concentrations for the aqueous phase of Portland cement before and after complex ion formation. They cited a "typical" molarity for calcium sulfate in the aqueous phase of Portland cement of $0.0258 \text{ mol L}^{-1}$. Using concentrations of sodium, calcium, sulfate, and hydroxide of 15, 57, 58, and 35 mmol L^{-1} , respectively, as reported by Bailey and Hampsen (1982), the GMIN model predicted the activity of water to be 0.99978. Substituting this water activity into Equation (3.3) yielded an estimate of the osmotic potential for cement of approximately -0.03 MPa (i.e., -306 cm). This value of osmotic potential was considered to be relatively small. Therefore, the total potentials inferred from the thermocouple psychrometer measurements for the Sandia concrete were related directly to matric potential (for calculating retention parameters) without any corrections for osmotic potential. The source of the retention and conductivity data for the concrete was PNL laboratory record books BNW 4042 and BNW 50881.

3.2.9 Groul

Bulk density, particle density, and hydraulic conductivity data are contained in Table A.8 of the Appendix. Saturated hydraulic conductivity was determined using the constant head method and

the Ruska permeameter with a pressure difference of 510 cm across the samples. Water retention by grout was determined using only the vapor equilibrium technique because the pressures required to remove water from this material were much greater than those that could be obtained with the other techniques. Water retention data for the DSSF grout are tabulated in Table A.9 in the Appendix.

The data reported by Lokken et al. (1992b) indicated that the molarity of the grout pore water solution was in excess of 4.0 mol L⁻¹. Because of the high molarity, the osmotic potential was calculated to correct the vapor adsorption data. The average concentrations of 6 of the 12 measured constituents (i.e., Na, K, NO₃, NO₂, SO₄, and Cl) from Table 3.1 in Lokken et al. (1992b) were used as input to the GMIN chemical equilibrium model (Felmy 1990) to estimate the activity of water in the DSSF grout pore solutions. The activity of water estimated by the GMIN code was 0.8448. Substituting this water activity into Equation (3.3) yielded an osmotic potential of approximately -23.2 MPa (-232 bar). This value of osmotic potential was subtracted from all total water potential data for the DSSF grouts to estimate the matric potentials reported in Table A.9. Implicit in this osmotic potential correction is the assumption that the osmotic potential of the grout will remain more or less constant and will not change as a function of saturation. The source of the retention and conductivity data for the DSSF grout was PNL laboratory record book BNW 53294.

4.0 HYDRAULIC PARAMETERS

Flow and transport through an unsaturated porous medium is governed by the relationships among water content, matric potential, and hydraulic conductivity. Within numerical models, these relationships can be represented by mathematical functions containing one or more fitted parameters. This section specifies the hydraulic functions used, the parameter fitting procedure, and the corrections for gravel content, and summarizes the average parameters to be used to describe the hydraulic properties of the materials in the conceptual model in Figure 2.3.

4.1 HYDRAULIC FUNCTIONS

The water retention function that was used was proposed by van Genuchten (1980) as follows:

$$\theta(h) = \theta_r + (\theta_s - \theta_r) [1 + (\alpha h)^n]^{-m} \quad (4.1)$$

where $\theta(h)$ = volumetric water content (dimensionless) as a function of h , the matric potential

θ_s = saturated water content (dimensionless)

θ_r = residual water content (dimensionless)

α = reciprocal of air-entry matric potential (cm^{-1})

h = matric potential (cm)

n, m = curve-fitting parameters (dimensionless), with $m=1-1/n$.

Describing water retention with the van Genuchten function enabled calculation of unsaturated hydraulic conductivity, $K(h)$, as follows (van Genuchten 1980):

$$K(h) = K_s \frac{\{1 - (\alpha h)^n [1 + (\alpha h)^n]^{-m}\}^2}{[1 + (\alpha h)^n]^{m/2}} \quad (4.2)$$

using the predictive hydraulic conductivity model of Mualem (1976). In Equation (4.2), the pore interaction term was fixed at a value of 0.5.

4.2 PARAMETER ESTIMATION PROCEDURE

The retention parameters θ_s , θ_r , α , and n from Equation (4.1) were fit to water retention data using the nonlinear, least-squares, curve-fitting program known as RETC (Yates et al. 1992).

Generally, the water retention data from the various measurement methods were combined and used to fit the parameters in the van Genuchten water retention function. When data from the pressure plate and hanging water column methods overlapped, the overlapping pressure plate data were omitted during the curve fitting because they were considered less reliable. Smoot et al. (1989) reported fitted parameters for samples from well No. 299-E25-234 in which the retention data from duplicate samples were combined before fitting. For this report, the water retention data from each duplicate subsample were refit individually to obtain fitted parameters. Therefore, the parameter estimates in the Appendix for samples from well No. 299-E25-234 vary somewhat from those reported in Smoot et al. (1989) and Connelly et al. (1992b).

The sandy sequence of the Hanford formation was represented by combining 28 sets of parameters from well No. 299-E25-234, 5 sets of parameters from the 241 AP Tank Farm Facility, 21 sets of parameters from the U.S. Ecology site, 3 sets of parameters from the 200-BP-1 site, and 3 values of in situ saturated hydraulic conductivity determined using a borehole permeameter at the bottom of the existing grout pit (Dames and Moore 1988).

The lower gravel sequence of the Hanford formation was represented by combining two sets of parameters from well No. 299-E25-234, eight sets of parameters from the 200-BP-1 site, two sets of parameters from B Pond, and two sets of parameters from the U.S. Ecology site. Some of the parameter sets were from samples of the upper gravel sequence of the Hanford formation, which is absent in the vicinity of the GTF. However, the upper and lower gravel sequences of the Hanford

formation are texturally similar and more or less indistinguishable from each other except for stratigraphic position (Connelly et al. 1992a, 1992b).

The Ringold Formation was represented by combining four sets of parameters from the Ringold Formation near B Pond and one set of parameters from the U.S. Ecology site. No data or sets of parameters were available for the Ringold Formation beneath the GTF.

Parameters for the backfill soil, clay, gravel, concrete, and grout were fitted to the data reported in the Appendix. Given the lack of data on asphalt properties, parameters for the asphalt were estimated. Parameter sets for all of the materials having more than one parameter set are reported in Tables A.10 to A.14 of the Appendix, along with the estimated means and variances.

4.3 CORRECTIONS FOR GRAVEL CONTENT

In a summary of the hydrogeology of the 200 East Area, Cushing (1992) mentioned the presence of gravel throughout portions of the vadose zone. Except for samples collected above the 126-ft (38.4-m) depth from well No. 299-E25-234, all water retention and hydraulic conductivity data used for this report were generated using the less than 2-mm-diameter particle-size fraction.

Bouwer and Rice (1983) proposed a technique for calculating the bulk hydraulic properties of a mixture containing sand and gravel from the hydraulic properties of the sand fraction alone and the volume fraction of the gravel. The water retention of the sand-gravel mixture was determined as follows:

$$\theta_b = (1 - V_r) \theta_s \quad (4.3)$$

where θ_b = volumetric water content of the sand-gravel mixture

θ_s = volumetric water content of the sand fraction

V_r = volume fraction of the gravel.

The bulk saturated hydraulic conductivity, K_b , of the sand-gravel mixture was calculated as

$$K_b = K_s (e_b / e_s) = K_s (\theta_b / \theta_s) (1 - \theta_s) / (1 - \theta_b) \quad (4.4)$$

where K_s = saturated hydraulic conductivity of the sand (less than 2-mm-diameter size fraction)

e_b = void ratio of sand-gravel mixture

e_s = void ratio of sand

and the void ratio is simply the volume of voids divided by the volume of solids. In Equation (4.4), θ_b and θ_s are the saturated values. Bouwer and Rice (1983) suggested that, in practice, the above procedure could be made more accurate if the saturated water content of the sand-gravel mixture was determined in situ. This value could then be used as a matching point when fitting parameters to describe the relationship between K and θ .

Equations (4.3) and (4.4) were used to scale the hydraulic properties of samples 1 and 4 from the 241-AP Tank Farm (Smoot et al. 1989). The scaled hydraulic properties were referenced as sample 1G and 4G, where the "G" indicated that the properties were scaled to account for the gravel fraction. Samples 1G and 4G contained 38% and 10% gravel, respectively. Thus, utilizing Equation (4.3), their effective θ_s values were reduced by 38% and 10%, respectively. Utilizing Equation (4.4), the K_s values were reduced by 51% and 17%, respectively, for samples 1G and 4G. For these calculations, the particle density of the gravel was assumed to equal that of the sediments. Similar corrections for gravel content were not performed for the samples representing the Hanford formation lower gravels.

4.4 PARAMETER SUMMARY

The average parameters for sediments from the Hanford and Ringold Formations and for the other materials comprising the grout waste isolation system are listed in Table 4.1. These parameters

TABLE 4.1. Average Water Retention Parameters and Vertical Saturated Hydraulic Conductivity Values Used for Grout Vadose Zone Flow and Transport Modeling

Material Type	Water Retention					Unsaturated Hydraulic Conductivity	
	No. of Samples	θ_s	θ_r	$\alpha \text{ cm}^{-1}$	n	No. of Samples	$K_s \text{ cm s}^{-1}$
Hanford Formation^(a)							
Sandy Sequence	57	0.4203	0.0234	0.1943	1.868	45	1.55×10^{-3}
Lower Gravels	14	0.3584	0.0213	0.0290	1.613	13	2.73×10^{-4}
Ringold Formation^(a)							
(undifferentiated)	5	0.4982	0.0283	0.0176	1.338	5	2.42×10^{-6}
Backfill Soil ^(b)	2	0.3710	0.0450	0.0683	2.080	2	3.00×10^{-2}
Gravel ^(b)	2	0.5180	0.0140	3.5366	2.661	1	1.85
Clay ^(b)	3	0.4480	0.0000	5.39×10^{-4}	1.324	3	9.40×10^{-9}
Asphalt ^(c)	0	0.162	0.0	1.00×10^{-7}	2.0	0	1.0×10^{-20}
Concrete ^(d)	6	0.2258	0.0000	7.61×10^{-6}	1.393	6	3.75×10^{-10}
DSSF Grout ^(e)	9	0.5781	0.0000	1.08×10^{-5}	1.650	3	1.47×10^{-8}

(a) Original data for well No. 299-E25-234 contained in laboratory record book BNW 52457; other data sources were Smoot et al. (1989), Connelly et al. (1992b), and Dames and Moore (1988).

(b) Original data contained in laboratory record book BNW 53071.

(c) Estimated parameters; no available data.

(d) Original data contained in laboratory record books BNW 4042 and BNW 50881.

(e) Original data contained in laboratory record book BNW 53294.

were used for the base-case flow and transport simulations for the grout PA. The parameters in Table 4.1 are arithmetic mean values with the exception of the K_s values, which are geometric mean values. Geometric mean values of the saturated hydraulic conductivities were used because saturated hydraulic conductivity has often been shown to be lognormally distributed (Hills and Wierenga 1991; Sudicky 1986).

Figures A.1 through A.16 show the retention and conductivity data along with the fitted functions for the samples from well No. 299-E25-234, the backfill soil, gravel, clay, concrete, and grout. Smoot et al. (1989) reported the data and a parameter set for each depth in Well E25-234, but they had lumped the data from individual samples to calculate the parameters. As noted previously in this report, each sample was fitted separately. Connelly et al. (1992b) reported plots of the remaining functions in Tables A.10 to A.12.

The water retention and hydraulic conductivity curves corresponding to the average parameters from Table 4.1 are shown in Figure 4.1. The saturated hydraulic conductivities of the different

FIGURE 4.1. Average Water Retention (a) and Hydraulic Conductivity (b) Curves. The parameters used to generate the curves are listed in Table 4.1.

materials depicted in Figure 4.1 range over 9 to 10 orders of magnitude. Similarly, the air-entry potentials (reciprocal of α) of these materials range over 6 to 7 orders of magnitude. Insufficient data were available to reliably determine representative probability distributions of the parameters for the sediments beneath the GTF. However, means, variances, and minimum and maximum values of the parameters were calculated for this limited number of samples to show the potential ranges of parameter variability.

5.0 DISCUSSION

The parameters in Table 4.1 were used in single-phase isothermal flow and transport simulations reported in the grout PA. Summarized here are the assumptions and observations that underlie the generation of those parameters and suggestions for improving the methods used to collect the data and generate new parameters. What is needed most is a program dedicated to identifying the important materials, identifying the conditions to which those materials will be subjected, and measuring the properties under those conditions. Burial of grouted and other defense wastes may eventually require simulations of two-phase nonisothermal flow with reactive transport. The effects of osmotic potential on the flow of water vapor may need to be coupled directly with either isothermal or nonisothermal liquid water flow. Creating a research program now would ensure that the appropriate hydraulic models are identified and parameters for simulations are obtained in a timely fashion.

5.1 METHODS

Overall, the data quality was not consistent. Some sources documented the sample location and reported a range of replicated tests that were well described and referenced; other sources provided only a number. Because the analysis methods have some leeway for interpretation and application, the precise methods used should be documented, along with the sample sizes. Ideally, undisturbed samples should be obtained and analyzed for particle size, particle size distribution (including gravel distribution and clay content), particle density, bulk density, water retention over the entire range of matric potentials, and saturated hydraulic conductivity (and at least one unsaturated conductivity value, if possible). Although not performed on the samples used in this report, chemical tests would reveal useful information such as CaCO_3 content and osmotic potential. All tests should be run in duplicate if not triplicate.

The backfill soil, clay, and asphalt warrant further testing because they are such prominent components of the near-field region of the vaults. The backfill soil was analyzed in duplicate compared

to the more than 50 samples used to represent the Hanford sandy sequence. The method used to measure retention in the backfill (i.e., a column method) remains to be verified by established procedures. The data for the backfill appear to vary significantly from the data for other similar materials; thus, more analyses are needed. For example, the saturated conductivity of the backfill was 10- to 100-fold higher than the values measured for intact cores from the Hanford formation that had almost identical particle size distributions and similar bulk density values. The value was also 100-fold higher than the K_s value for stockpile samples reported by Dames and Moore (1988).

The clay was actually a bentonite/silt mix with the propensity to swell considerably (as demonstrated in the lab). As noted in Section 3.2.6, the K_s of the swelled clay (about 2×10^{-7} cm s⁻¹) was 20 times higher than originally measured. The properties of the clay must be evaluated under the expected conditions, i.e., under a load, under a large temperature cycle as the grout temperature rises and subsides, and under drying. Some test results were reported by Dames and Moore (1988), but the methods and testing ranges must be examined. For the grout PA, the properties used to simulate water behavior in the asphalt barrier were assumed. The properties of the asphalt in its original and degraded states should also be measured and reported.

The properties of the concrete were determined on a sample from Sandia National Laboratories. Some measurements of the properties of the concrete to be used at the GTF must be made to verify the similarity to the Sandia sample. If the properties are not similar, the GTF concrete properties should be evaluated fully.

The properties for DSSF grout were determined for a special formulation. For reasons related to the need to optimize parameters such as leachability and strength, the formulation is subject to revision. Lokken and Martin (1992) discussed DSSF grout formulations in which the ratios of blast furnace slag, cement, fly ash, and limestone flour, and two dilutions of the tank waste, were tested for their effects on properties. As the grout formulation is varied, the resulting grout should be evaluated

for the need to conduct physical and hydraulic tests specific to that formulation, as much as two separate soil samples are treated separately or together depending on their similarities.

Measurements of the physical and hydraulic properties of DSSF grout could be affected by changes in the pore solution and grout structure as the samples are dried (e.g., precipitation near surfaces) or water is passed through (e.g., K_s test). The measurement techniques need to be evaluated to determine whether or not such changes have a significant effect on the measurement of properties. During the design life of the GTF, the grout material will experience similar changes or degradation; the results from the evaluation of measurement techniques will be transferable to the evaluation of degradation.

5.2 BULK DENSITY

Table A.2 shows how bulk density varied with depth within the same formation (Smoot et al. 1989). Most of the data used to fit parameter values were derived from samples that were not packed to the in situ bulk densities, which were unknown, the packed samples certainly did not have the structure of the in situ sediment material.

Sample size may have affected the observations of bulk densities. The conductivity cores in Table A.2 were roughly 40 times larger in volume than the water retention cores. Table A.2 shows that the mean bulk density value of the conductivity cores was 0.15 g/cm^3 (i.e., 10%) greater than that of the water retention cores. The difference in bulk density was either the result of the subsampling technique or the indirect method used to calculate the bulk density of the conductivity core.

5.3 HYDRAULIC CONDUCTIVITY

For each material, the predicted hydraulic conductivities reported in the Appendix range from over 3 to 4 orders of magnitude near saturation and more than 10 orders of magnitude near the residual or irreducible water content. However, it should be noted that the unsaturated hydraulic

conductivity curves were generated using the saturated hydraulic conductivity as a single matching point. Therefore, there is much more uncertainty in the predicted unsaturated hydraulic conductivity values at lower water contents.

Yates et al. (1992) compared measurements of unsaturated hydraulic conductivity for 23 different soils with predicted values generated using water retention and saturated hydraulic conductivity data with the RETC code and the Mualem model. In general, the predicted unsaturated hydraulic conductivity values were in reasonable agreement with the actual hydraulic conductivity data. Rockhold et al. (1988) compared measured and predicted unsaturated hydraulic conductivities for a sandy soil on the Hanford Site using field and laboratory data. The comparisons indicated differences of up to one order of magnitude between unsaturated hydraulic conductivities predicted using only water retention data and saturated hydraulic conductivity with the Mualem model and the RETC code, and actual unsaturated hydraulic conductivity data generated using the steady-state flux control method in laboratory column experiments (Klute and Dirksen 1986). The lack of unsaturated hydraulic conductivity data for the materials in the grout PA precluded direct comparisons of measured and predicted unsaturated hydraulic conductivities.

5.4 GRAVEL CONTENT

Gravel is a constituent of much of the vadose zone. The percentages of gravel should always be reported. The higher the percentage of gravel, the more important it is to measure the particle density of the gravel fraction. Scaling the hydraulic properties of two samples with high percentages of gravel significantly reduced the values of effective porosity and saturated hydraulic conductivity relative to the values determined using the less than 2-mm particle-size fraction. The accuracy of this method for scaling the hydraulic properties to account for the gravel-size fraction should be verified for the materials in the grout PA. This method or an analogous procedure should, however, be consistently applied to correct the hydraulic properties of all samples containing a measurable gravel content.

5.5 SPATIAL VARIABILITY

The intact sediment cores from well No. 299-E25-234 were lined and did not permit visual examination. Thus, lenses and stratifications noted in the driller's log were not observed in the cores, even though those features may have been present. Two subsamples, one from each end of each core, were used to represent the entire core. Of 13 intact cores, nine cores yielded retention data for two subsamples that were consistent for each end of the core. In contrast, four cores yielded subsamples with a large degree of variability. For one of those cores (Sample 25), a second set of hanging water column tests was conducted to see if the first set was an anomaly. The results from those tests indicated that, indeed, a significant variation in properties indeed existed within Sample 25 over a distance of 4 cm (Smoot et al. 1989).

Based on the laboratory results, heterogeneity on the scale of the individual conductivity cores (15 cm diameter; 15 cm long) evidently existed. The question of what is the correct scale of measurement necessary to quantify the spatial variability and determine effective flow parameters remains a research topic. However, it may be possible to correlate data obtained from geophysical logging techniques and granulometric (i.e., particle size) data to more clearly delineate lenses and stratifications that control the flow and transport processes.

Insufficient data were available to reliably estimate spatial correlation lengths for the hydraulic properties of the sediments beneath the GTF. If such data were available, conditional simulations could potentially be used to forecast the transport of contaminants from the grout vaults (Journel and Huijbregts 1978; Clifton and Neuman 1982). Conditional simulation allows spatially correlated random hydraulic property fields to be generated with the proper spatial and statistical structures and preserves the values of the field observations at their measurement locations. This type of simulation can be carried out using the Monte Carlo method to generate probabilistic assessments of contaminant migration and fate. Various other techniques for incorporating data and parameter uncertainties into performance assessment models are described by Zimmerman et al. (1990).

5.6 HYSTERESIS

Hysteresis effects were shown to be significant during transient unsaturated flow (Kaluarachchi and Parker 1987; Lenhard and Parker 1987). However, none of the numerical models used for the grout PA simulations accounted for hysteresis in the constitutive relationships describing water retention or conductivity and no data were collected to support such modeling. Given the burial depth, however, the extent of wetting and drying cycles (when hysteresis is manifested) should be minimal. One or more simulations could be conducted to verify the veracity of this assumption. The analysis is not straightforward, however, because the current simulations do not address the movement of water vapor in response to the temperature pulse and osmotic effects, which are likely to be the two major drivers of water content changes.

5.7 ANISOTROPY

In the groundwater hydrology literature it is common to see references to regional anisotropy, with saturated hydraulic conductivities in the horizontal direction that are 10 or more times greater than those in the vertical direction (Freeze and Cherry 1979). Apparent anisotropy results from the preferred orientation of mineral grains in the horizontal direction and from material heterogeneities (Freeze and Cherry 1979; Marcus and Evenson 1961). Laboratory measurements of saturated hydraulic conductivity generally represent the vertical direction because of the vertical orientation of the samples. Hydraulic conductivities calculated from aquifer test data are more representative of the horizontal direction, and integrate much larger sample volumes. Such tests, however, apply only to the saturated zone of the aquifer and not to the vadose zone.

Graham et al. (1981) reported conductivities in the 200 Area of 0.7 to 3.5 cm s⁻¹ in the Hanford formation, 0.003 to 0.08 in the middle Ringold Formation, and 0.001 to 0.004 in the lower Ringold Formation. They determined an anisotropy ratio in one well that ranged between 16 and 13. Analyses of aquifer test data from the 200 East Area indicated that saturated hydraulic conductivities in the lower gravel sequence of the Hanford formation and the Ringold Formation (gravel unit A)

ranged from approximately 0.7 to 6.8 cm s⁻¹ (Newcomer et al. 1992). These values were 4 to 8 orders of magnitude greater than the range of values determined using laboratory methods. This discrepancy was attributed to anisotropy, heterogeneity, and scale differences resulting from different sampling volumes. Also, when collecting split spoon samples, sediments may be compacted during drilling, producing lower saturated hydraulic conductivities. Neither laboratory nor field measurements of horizontal conductivity values in the vadose zone of the GTF were available. Without supporting field data, the selection of anisotropy ratios for the vadose zone would be arbitrary. Therefore, hydraulic conductivities were assumed to be isotropic for the vadose zone flow and transport simulations that were conducted for this grout PA. To support the use of anisotropy ratios in the vadose zone, measurements of conductivity are needed in both the horizontal and vertical directions on the same undisturbed samples without observable sediment layering or preferred channels. In lieu of measurements, transient flow data are needed that can be used to calibrate flow and transport models with the anisotropy ratio as a calibration parameter.

5.8 TEMPERATURE AND SOLUTE EFFECTS

The testing and analyses reported here did not account for the effects of temperature changes and solutes on the physical and hydraulic properties of the grout and other materials at the GTF. Temperatures in the grout were expected to reach 90°C and above. The solute content of the pore water in DSSF grout was shown to exceed 400 g L⁻¹ (Lokken et al. 1992b). Such high temperatures and solute contents will affect the conductivity of water, the retention of water, the water vapor pressure, and the volume of clays.

The conductivity of water in a porous medium is a function of density and viscosity, which in turn are functions of temperature. Density changes over temperature ranging from 0°C to 100°C are no more than 4% and likely exert a minor effect on predictions of flow and transport. Viscosity changes over the same range, however, are roughly $\pm 75\%$ relative to the viscosity at 20°C. The effect of temperature on viscosity might be accounted for by varying saturated conductivity $\pm 75\%$,

although such an analysis would ignore all of the associated effects caused by temperature changes (e.g., vapor pressure changes, solubility changes). Whether the temperature dependence of viscosity explains all of the temperature dependence of unsaturated conductivity is an unresolved issue (Constantz 1982; Hopmans and Dane 1986).

At a constant temperature, the conductivity of water is inversely related to the kinematic viscosity. For a NaNO_3 concentration of 367 g L^{-1} , comparable to those seen by Lokken et al. (1992b), the relative kinematic viscosity would be 1.3, meaning a 23% reduction in conductivity. This reduction appears to be less significant than the changes in viscosity caused by temperature, and certainly smaller than the natural variability of conductivity. For these reasons, viscosity changes were not considered in the grout PA.

Temperature also affects water retention through its dependence on surface tension (between 0°C and 100°C , surface tension varies $\pm 12\%$ from the value at 50°C). The measured effect, however, is much greater; Constantz (1982) reported that retention was reduced 3- to 4-fold more than predicted from surface tension alone as the temperature was increased from 2°C to 25°C to 45°C . Giakoumakis and Tsakiris (1991) saw a similar response in retention between 3°C and 20°C for both drying and wetting experiments.

Vapor flow is affected by osmotic potentials and temperature gradients, both of which will be highest in and around the vaults. Vapor flow resulting from the osmotic potential gradient was estimated and considered in the grout PA. A conservative analysis showed the impact to be much lower than the impact of liquid flow. Vapor flow resulting from a temperature gradient is most likely to be highest during the early years of the GTF and then decrease in importance as the GTF cools. To understand the effect of temperature on vapor flow, consider that the vapor pressure of water approximately doubles as the temperature is raised from 0°C to 10°C , then doubles again at the following temperatures: 21°C , 33°C , 45°C , 60°C , 75°C , and 93°C . Nasser et al. (1992) reported the results of

experiments and modeling dealing with the combined effects of heat, water, and solutes in porous media. They looked at temperatures between 9°C and 27°C. Their model performed best at matching the experimental results when the initial water contents were high (0.134 to 0.166 cm³ cm⁻³) and the initial solute concentration was low (< 0.1 mol). When the water contents were low, or when the solute concentration was high (i.e., 0.5 mol), the model either underestimated or overestimated water flow. Their results indicate an incomplete understanding of the physics and chemistry of their system. By implication, their results are likely applicable to the GTF, which could see temperatures near 90°C and solute concentrations above 4.0 mol. An analysis should be conducted to determine whether the experiment-model discrepancies, when scaled to the conditions of the GTF, would have a significant impact on the grout PA.

Clay-size particles have the greatest likelihood for volume changes from flocculation or dispersion caused by the presence of solutes. The volume changes induced in the surrounding sediments by contact with the grout solution is unknown. The clay contents seen in most of the sediment samples were small; for the samples reported in the Appendix, the clay contents were 6% or less. Laboratory tests should be conducted in which the materials (i.e., the concrete, asphalt, and sediments) are subjected to grout pore water and observed for geochemical changes, physical changes, and hydraulic changes.

5.9 GEOCHEMISTRY

The testing and analyses reported here did not account for the effects of geochemical changes in the GTF, particularly within, and in the vicinity of, the grout vaults. These changes will be brought on by precipitation/dissolution reactions as the high-concentration grout pore water interacts with the low-concentration sediment pore water and by the temperature and water content variations experienced by the materials of the GTF over their lifetime. The precipitation/dissolution reactions will cause volume changes that can lead to cracks or the plugging of cracks and pores (e.g., see Lowell et al. [1993] for an example of permeability affected by precipitation). In either case, the physical

and hydraulic properties will be changed. Criscenti and Serne (1988) studied the geochemistry of a grouted commercial waste form in contact with soil, but they did not explore the associated physical and hydraulic changes. A literature review and laboratory tests of the actual grout formulations and wastes of the GTF should be conducted to determine the geochemical effects on physical and hydraulic properties.

5.10 DEGRADATION

The testing and analyses reported here did not account for the effects of material degradation, which is defined as any change from the original properties. During the course of compiling the PA, many mechanisms for degradation were proposed that could only be addressed with gross approximations or estimates. Examples include 1) fines infiltrating the gravel and negating the capillary break, 2) concrete spalling and cracking that creates flow pathways within the vault and through the concrete wall, 3) loss of the asphalt to vaporization and biodegradation, leaving only the aggregate mix, and 4) cracking of the asphalt after it becomes brittle from the heat. All proposed degradation mechanisms should be evaluated for validity and impact; those mechanisms that are valid and could significantly affect the PA must be the subject of further tests. An accurate assessment, based on testing, should be made of the rates of degradation and the associated changes in the physical and hydraulic properties.

6.0 REFERENCES

Angus, M. J. and F. P. Glasser. 1985. "The Chemical Environment in Cement Matrices." Mat. Res. Soc. Symp. Proc. 50:547-556.

American Society for Testing and Materials. 1985. "Standard Test Method for Particle-size Analysis of Soils. D 422-63 (1972)." 1985 Annual Book of ASTM Standards 04.08:117-127. American Society for Testing and Materials, Philadelphia.

Bailey, J. E. and C. J. Hampsen. 1982. "The Chemistry of the Aqueous Phase of Portland Cement." Cement and Concrete Res. 12:227-236.

Blake, G. R. and K. H. Hartge. 1986a. "Particle Density." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 377-382. American Society of Agronomy, Madison, Wisconsin.

Blake, G. R. and K. H. Hartge. 1986b. "Bulk Density." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 363-375. American Society of Agronomy, Madison, Wisconsin.

Bouwer, H. and R. C. Rice. 1983. "Effect of Stones on Hydraulic Properties of Vadose Zones." In Proceedings of the Characterization and Monitoring of the Vadose (Unsaturated) Zone. National Water Well Association, Worthington, Ohio.

Clemmer, R. G., R. P. Allen, and L. K. Fetrow. 1992. Hydrogen Permeation of Asphalt Test Results - FY-1992, Hanford Grout Technology Program. HGTP392-0605-02, Pacific Northwest Laboratory, Richland, Washington.

Clifton, P. M. and S. P. Neuman. 1982. "Effects of Kriging and Inverse Modeling on Conditional Simulation of the Arva Valley Aquifer." Water Resour. Res. 18:1215-1234.

Connelly, M. P., B. H. Ford, and J. V. Borghese. 1992a. Hydrogeologic Model for the 200 West Groundwater Aggregate Area. WHC-SD-EN-TI-014, Westinghouse Hanford Company, Richland, Washington.

Connelly, M. P., B. H. Ford, J. V. Borghese, S. Trent, and J. Lindberg. 1992b. Hydrogeologic Model for the 200 East Groundwater Aggregate Area. WHC-SD-EN-TI-019, Westinghouse Hanford Company, Richland, Washington.

Constantz, J. 1982. "Temperature Dependence of Unsaturated Conductivity of Two Soils." Soil Sci. Soc. Am. J. 46:466-470.

Corey, A. T. and A. Klute. 1985. "Application of the Potential Concept to Soil Water Equilibrium and Transport." Soil Sci. Soc. Am. J. 49:3-11.

Criscenti, L. J. and R. J. Serne. 1988. Geochemical Analysis of Leachates from Cement/Low-Level Radioactive Waste/Soil Systems. PNL-6544, Pacific Northwest Laboratory, Richland, Washington.

Cushing, C. E. 1992. Hanford Site National Environmental Policy Act (NEPA) Characterization. PNL-6415, Rev. 5, Pacific Northwest Laboratory, Richland, Washington.

Dames and Moore. 1988. "Geotechnical and Corrosion Investigation, Grout Vaults, Hanford, Washington." October 10, 1988. Report for Kaiser Engineers, Inc, by Dames and Moore, Seattle, Washington. Contract No. 10805-282-016.

Felmy, A. R. 1990. GMIN: A Computerized Chemical Equilibrium Model Using a Constrained Minimization of the Gibbs Free Energy. PNL-7281, Pacific Northwest Laboratory, Richland, Washington.

Freeze, R. A. and J. A. Cherry. 1979. Groundwater. Prentice-Hall, Inc., Englewood Cliffs, New Jersey.

Gee, G. W. and J. W. Bauder. 1986. "Particle-Size Analysis." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 383-409. American Society of Agronomy, Madison, Wisconsin.

Giakoumakis, S. G. and G. P. Tsakiris. 1991. "Eliminating the Effect of Temperature from Unsaturated Soil Hydraulic Functions." J. Hydrol. 129:109-125.

Graham, M. J., M. D. Hall, S. R. Strait, and W. R. Brown. 1981. Hydrology of the Separations Area. RHO-ST-42, Rockwell Hanford Operations, Richland, Washington.

Greenspan, L. 1977. "Humidity Fixed Points of Binary Saturated Aqueous Solutions." J. Res. Natl. Bur. Stand. Sect. A, 81:201-203.

Harvie, C. E., N. Møller, and J. H. Weare. 1984. "The Prediction of Mineral Solubilities in Natural Waters: The Na-K-Mg-Ca-H-Cl-SO₄-OH-HCO₃-CO₃-H₂O System in High Ionic Strengths at 25°C." Geochim. Cosmochim. Acta 48:723-751.

Hillel, D. 1982. Introduction to Soil Physics. Academic Press, Inc., Orlando, Florida.

Hills, R. G. and P. J. Wierenga. 1991. Model Validation at the Las Cruces Trench Site. NUREG/CR-5716, U. S. Nuclear Regulatory Commission, Washington, D. C.

Hopmans, J. W., and J. H. Dane. 1986. "Temperature Dependence of Soil Hydraulic Properties." Soil Sci. Soc. Am. J. 50:4-9.

Journel, A. G. and Ch. J. Huijbregts. 1978. Mining Geostatistics. Academic Press, Inc., London.

Kaluarachchi, J. J. and J. C. Parker. 1987. "Effects of Hysteresis with Air Entrapment on Water Flow in the Unsaturated Zone." Water Resour. Res. 23:1967-1976.

Klute, A. 1986. "Water Retention: Laboratory Methods." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 635-660. American Society of Agronomy, Madison, Wisconsin.

Klute, A. and C. Dirksen. 1986. "Hydraulic Conductivity and Diffusivity: Laboratory Methods." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 687-732. American Society of Agronomy, Madison, Wisconsin.

Lenhard, R. J. and J. C. Parker. 1987. "A Model for Hysteretic Constitutive Relations Governing Multiphase Flow: 2. Permeability-Saturation Relations." Water Resour. Res. 3:2197-2206.

Lokken, R. O. and P. F. C. Martin. 1992. Durability of Double-Shell Slurry Feed Grouts: FY-90 Results. PNL-7838, Pacific Northwest Laboratory, Richland, Washington.

Lokken, R. O., P. F. C. Martin, and J. W. Shade. 1992a. Characterization of Double-Shell Slurry Feed Grout Produced in a Pilot-Scale Test. PNL-7979, Pacific Northwest Laboratory, Richland, Washington.

Lokken, R. O., P. F. C. Martin, and J. W. Shade. 1992b. Durability of Double-Shell Tank Waste Grouts. PNL-7835, Pacific Northwest Laboratory, Richland, Washington.

Lowell, R. P., P. van Cappellen, and L. N. Germanovich. 1993. "Silica Precipitation in Fractures and the Evolution of Permeability in Hydrothermal Upflow Zones." Science 260:192-194.

Marcus, H. and D. E. Evenson. 1961. Directional Permeability in Anisotropic Porous Media. Water Resour. Center, Contrib. No. 31, Univ. of California, Berkeley, California.

Mualem, Y. 1976. "A New Model for Predicting the Hydraulic Conductivity of Unsaturated Porous Media." Water Resour. Res. 12:513-522.

Murphy, E. M., J. E. Szecsody, and S. J. Phillips. 1991. A Study Plan for Determining Recharge Rates at the Hanford Site Using Environmental Tracers. PNL-7626, Pacific Northwest Laboratory, Richland, Washington.

- Nasser, I. N., R. Horton, and A. M. Globus. 1992. "Simultaneous Transfer of Heat, Water, and Solute in Porous Media: II. Experiment and Analysis." Soil Sci. Soc. Am. J. 56:1357-1365.
- Newcomer, D. R., M. A. Chamness, D. L. McAlister, R. J. Brockman, A. W. Pearson, and S. T. Teel. 1992. Unconfined Aquifer Hydrologic Test Data Package for the 200 East Area. WHC-SD-EN-TI-030, Westinghouse Hanford Company, Richland, Washington.
- Pitzer, K. S. 1973. "Thermodynamics of Electrolytes I: Theoretical Basis and General Equations." J. Phys. Chem. 77:268-277.
- Pitzer, K. S. 1979. Activity Coefficients in Electrolyte Solutions. CRC Press, Boca Raton, Florida.
- Rawlins, S. L. and G. S. Campbell. 1986. "Water Potential: Thermocouple Psychrometry." In Methods of Soil Analysis, Part 1, ed. A. Klute, pp. 597-617. American Society of Agronomy, Madison, Wisconsin.
- Reardon, E. J. 1990. "Anion Interaction Model for the Determination of Chemical Equilibria in Cement/Water Systems." Cement and Concrete Res. 20:175-192.
- Rockhold, M. L., M. J. Fayer, and G. W. Gee. 1988. Characterization of Unsaturated Hydraulic Conductivity at the Hanford Site. PNL-6488, Pacific Northwest Laboratory, Richland, Washington.
- Smoot, J. L., J. E. Szecsody, B. Sagar, G. W. Gee, and C. T. Kincaid. 1989. Simulations of Infiltration of Meteoric Water and Contaminant Plume Movement in the Vadose Zone at Single-Shell Tank 241-T-106 at the Hanford Site. WHC-EP-0332, Westinghouse Hanford Company, Richland, Washington.
- Sposito, G. 1986. "The Physics of Soil Water Physics." Water Resour. Res. 22:83S-88S.
- Sudicky, E. A. 1986. "A Natural Gradient Experiment on Solute Transport in a Sand Aquifer: Spatial Variability and its Role in the Dispersion Process." Water Resour. Res. 22:2069-2082.
- Taylor, S. A. and G. L. Ashcroft. 1972. Physical Edaphology: The Physics of Irrigated and Non-irrigated Soils. W. H. Freeman and Company, San Francisco.
- van Genuchten, M. Th. 1980. "A Closed-Form Equation for Predicting the Hydraulic Conductivity of Unsaturated Soils." Soil Sci. Soc. Am. J. 44:892-898.
- Whiting, D. 1988. "Permeability of Selected Concretes." In Permeability of Concretes, ed. D. Whiting and A. Walitt, pp. 195-222. SP-108, American Concrete Institute, Detroit, Michigan.

Yates, S. R., M. Th. van Genuchten, A. W. Warrick, and F. J. Leij. 1992. "Analysis of Measured, Predicted, and Estimated Hydraulic Conductivity Using the RETC Computer Program." Soil Sci. Soc. Am. J. 56:347-354.

Zimmerman, D. A., K. K. Wahl, A. L. Gutjahr, and P. A. Davis. 1990. A Review of Techniques for Propagating Data and Parameter Uncertainties in High-Level Radioactive Waste Repository Performance Assessment Models. NUREG/CR-5393, SAND89-1432, Sandia National Laboratories, Albuquerque, New Mexico.

APPENDIX

PHYSICAL AND HYDRAULIC PROPERTY DATA

APPENDIX

PHYSICAL AND HYDRAULIC PROPERTY DATA**TABLE A.1.** Particle-Size Distribution Data for Sediment Samples from Well No. 299-E25-234. For two samples with gravel contents >10%, 1-kg samples were wet sieved to determine gravel size distribution.

<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>	<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>
<u>5</u>	2000.00	98.93	<u>19</u>	2000.00	98.23
1% Gravel	1000.00	91.18	2% Gravel	1000.00	95.57
88% Sand	500.00	56.55	62% Sand	500.00	88.01
7% Silt	250.00	25.88	31% Silt	250.00	69.84
4% Clay	106.00	15.15	5% Clay	106.00	47.35
	75.00	12.55		75.00	41.19
	53.00	10.67		53.00	36.33
	48.72	10.13		48.20	21.13
	28.21	8.75		28.11	16.63
	15.48	7.75		15.51	13.25
	8.93	6.88		8.99	9.88
	6.32	5.00		6.36	7.63
	5.15	4.25		5.22	5.25
	4.47	3.63		4.52	5.50
	1.31	3.62		1.32	5.25
<u>25</u>	2000.00	99.74	<u>29</u>	2000.00	99.84
86% Sand	1000.00	97.07	95% Sand	1000.00	98.16
9% Silt	500.00	85.07	2% Silt	500.00	77.67
5% Clay	250.00	51.27	3% Clay	250.00	40.23
	106.00	21.97		106.00	11.83
	75.00	16.98		75.00	7.74
	53.00	13.83		53.00	4.75
	49.19	19.00		49.96	13.38
	28.66	14.88		29.07	9.50
	15.84	10.75		15.97	8.00
	9.19	8.13		9.22	6.75
	6.48	6.00		6.54	2.88
	5.28	6.00		5.33	3.25
	4.58	5.00		4.62	2.63
	1.34	4.63		1.35	2.75

TABLE A.1. (contd)

<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>	<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>
<u>37</u>	2000.00	98.63	<u>46</u>	2000.00	99.56
1% Gravel	1000.00	92.71	04% Sand	1000.00	97.57
77% Sand	500.00	81.34	4% Silt	500.00	73.37
17% silt	250.00	55.50	3% Clay	250.00	27.39
5% Clay	106.00	32.19		106.00	12.06
	75.00	26.92		75.00	9.78
	53.00	23.24		53.00	8.43
	50.18	21.25		51.33	6.50
	29.21	17.25		29.69	5.38
	16.07	15.38		16.26	4.75
	9.36	10.5		9.38	4.50
	6.62	8.75		6.61	4.25
	5.41	7.00		5.39	3.63
	4.68	6.63		4.66	2.50
	1.37	5.00		1.39	2.75
 <u>54</u>	 2000.00	 99.47	 <u>69</u>	 2000.00	 96.98
1% Gravel	1000.00	96.62	3% Gravel	1000.00	85.03
82% Sand	500.00	81.48	90% Sand	500.00	49.98
11% Silt	250.00	48.28	5% Silt	250.00	26.30
6% Clay	106.22	31.02	2% Clay	106.00	15.97
	75.00	26.75		75.00	13.55
	53.00	23.63		53.00	11.80
	50.11	17.75		50.29	7.00
	29.12	15.75		29.05	6.75
	16.05	12.00		15.92	5.25
	9.30	8.88		9.22	3.25
	6.59	7.88		6.53	2.50
	5.37	7.00		5.33	2.75
	4.65	7.38		4.62	2.00
	1.34	6.00		1.34	2.00

WHC-SD-WM-EE-004, Rev. 0

TABLE A.1. (contd)

<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>	<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>
<u>83</u>	2000.00	95.92	<u>99</u>	2000.00	99.51
4% Gravel	1000.00	79.70	58% Sand	1000.00	97.07
85% Sand	500.00	47.85	40% Silt	500.00	86.13
9% Silt	250.00	26.15	2% Clay	250.00	66.46
2% Clay	106.22	15.36		106.00	49.42
	75.00	12.74		75.00	44.97
	53.00	11.00		53.00	42.31
	49.93	7.13		49.84	8.49
	28.86	6.75		28.98	6.28
	15.85	5.63		15.93	4.76
	9.19	4.00		9.25	2.97
	6.51	3.00		6.55	2.63
	5.32	2.00		5.36	1.87
	4.61	2.00		4.65	1.70
	1.33	2.25		1.34	2.72
 <u>110</u>	 2000.00	 93.82	 <u>117</u>	 2000.00	 96.54
6% Gravel	1000.00	71.65	3% Gravel	1000.00	93.32
81% Sand	500.00	45.45	86% Sand	500.00	59.69
11% Silt	250.00	29.70	8% Silt	250.00	35.33
2% Clay	106.00	16.81	3% Clay	106.00	19.87
	75.00	15.32		75.00	15.98
	53.00	13.32		53.00	13.24
	49.91	8.75		50.49	10.13
	28.89	7.38		29.20	9.00
	15.88	5.88		16.06	6.25
	9.20	4.63		9.27	6.75
	6.52	3.00		6.56	4.50
	5.33	2.00		5.35	4.50
	4.62	1.75		4.64	3.75
	1.34	2.75		1.34	2.63

TABLE A.1. (contd)

<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>	<u>Sample</u>	<u>Particle Size μm</u>	<u>% Less Than</u>
126	2.00 (in)	100.00	133	2.00 (in)	100.00
51% Gravel	1.00 (in)	84.19	30% Gravel	1.00 (in)	100.00
39% Sand	0.75 (in)	71.72	48% Sand	0.75 (in)	98.50
9% Silt	0.50 (in)	66.80	19% Silt	0.50 (in)	89.38
1% Clay	4.75 (mm)	58.31	3% Clay	4.75 (mm)	80.70
	2000.00	48.78		2000.00	69.88
	1000.00	36.60		1000.00	57.57
	500.00	22.56		500.00	45.30
	250.00	16.07		250.00	36.77
	106.22	11.84		106.22	28.21
	75.00	10.78		75.00	25.00
	53.00	10.06		53.00	22.24
	50.24	2.13		47.41	15.82
	29.03	2.01		27.68	12.41
	15.90	2.01		15.31	9.79
	9.21	1.22		8.94	5.86
	6.51	1.16		6.35	4.20
	5.33	0.98		5.20	3.41
	4.62	0.55		4.51	3.15
	1.34	0.49		1.30	3.32

WHC-SD-WM-EE-004, Rev. 1

TABLE A.2. Bulk and Particle Density Data for Samples from Well No. 299-E25-234. Sample volumes were 68 cm³ for the retention cores and 2600 cm³ for the conductivity cores. Particle density values are the average of three replicates, except for samples 19 and 117, which are averages of two replicates.

Sample	Bulk Density (g cm ⁻³)	Conductivity Cores	Particle Density (g cm ⁻³)
	<u>Water Retention Cores</u>		
5	1.62, 1.75	1.79	2.82
19	1.45, 1.36	1.61	2.77
25	1.36, 1.31, 1.34, 1.31	1.43	2.72
29	1.53, 1.50	1.83	2.71
37	1.27, 1.29	1.38	2.64
46	1.44, 1.61	1.72	2.68
54	1.47, 1.42	1.66	2.68
69	1.70, 1.62	1.82	2.72
83	1.65, 1.68	1.80	2.73
99	1.71, 1.69	1.84	2.70
110	1.55, 1.58	1.89	2.72
117	1.47, 1.59	1.44	2.71
126	1.80, 1.76	1.82	2.79
133	<u>1.97, 1.96</u>	<u>2.03</u>	<u>2.73</u>
Mean Values ^a	= 1.53	1.68	2.72

(^a) Water retention cores for samples 126 and 133 were packed in the laboratory. Therefore, bulk densities at these two depths were not included in the calculation of mean bulk density.

TABLE A.3. Particle Size Distribution and Water Retention Data for Backfill Soil. Bulk density was 1.65 g cm⁻³. Particle density was assumed to be 2.8 g cm⁻³.

<u>Particle Size Distribution</u>		<u>Matric</u>	<u>Water Content,</u>	<u>Method</u>
<u>Diameter</u>	<u>% Less Than</u>	<u>Potential, -cm</u>	<u>cm³ cm⁻³</u>	
2000	99.47	0	0.36	Estimated
1000	94.0	5	0.358	Column; mean of 2 reps
500	55.52	15	0.304	"
250	24.0	25	0.181	"
106	15.32	35	0.133	"
75	13.33	45	0.127	"
53	11.73	55	0.116	"
50.1	12.0	65	0.115	"
28.95	12.25	75	0.119	"
15.92	10.0	85	0.113	"
9.213	8.25	95	0.108	"
6.529	7.25	102	0.071	Pressure Plate; mean of 3 reps
5.324	7.25	306	0.068	"
4.611	7.25	1020	0.066	"
1.339	5.5	3060	0.055	"
		31180	0.056	?
		103200	0.05	?
		812600	0.031	?
		1511000	0.023	?
		2483000	0.018	?

TABLE A.4. Water Retention Data for Gravel. Bulk density was 1.38 g cm⁻³. Particle density was assumed to be 2.8 g cm⁻³.

<u>Matric</u>	<u>Water Content</u>	<u>Method</u>
<u>Potential, -cm</u>	<u>cm³ cm⁻³</u>	
0	0.51	Estimated from bulk and particle densities
0.5	0.14	Column; mean of 2 reps
1	0.1	Interpolated from column data at 0.5 and 1.5 cm
1.5	0.075	Column; mean of 2 reps
2.5	0.044	"
5	0.017	Interpolated from column data at 4.5 and 5.5 cm (not shown)
10	0.01	Extrapolated from column data at 8.5 cm (not shown)
100	0.0095	Interpolated between values at 10 and 3.0E6 cm
1000	0.009	"
10000	0.0088	"
100000	0.0083	"
1000000	0.007	"
3000000	0.004	Vapor adsorption

TABLE A.5. Water Retention Data for Clay (i.e., a 1:3 Bentonite/Silt Loam Mix). The bulk density was 1.45 g cm^{-3} . The particle density was assumed to be 2.6 g cm^{-3} .

Matric Potential, -cm	Water Content, $\text{cm}^3 \text{ cm}^{-3}$	Method
0	0.442	Estimated from bulk and particle densities
10	0.442	Assumed value
102	0.442	Pressure plate value of 0.66 exceeded porosity; reset to porosity
306	0.442	Pressure plate value of 0.61 exceeded porosity; reset to porosity
1020	0.44	Pressure plate
3060	0.31	"
12400	0.258	Vapor adsorption
23600	0.188	"
291000	0.101	" (average of two samples at different potentials)
1920000	0.028	"

TABLE A.6. Bulk and Particle Density and Saturated Hydraulic Conductivity Data for Concrete. Sample diameters ranged from 1.400 to 1.408 cm. Particle densities estimated from bulk densities and calculated values of saturated water content (Table A.7). Conductivity values for samples D, E, and F were determined in the opposite direction used for samples A, B, and C.

Sample	Sample Length, cm	Sample Volume, cm^3	Bulk Density, g cm^{-3}	Estimated Particle Density, g cm^{-3}	Saturated Conductivity		
					Total Flow, cm^3	Total Time of all Tests, h	Average Test Value, cm s^{-1}
CL-40A	1.155	1.78	2.08	2.57	0.25	72	3.55E-10
CL-40B	1.146	1.78	2.02	2.59	0.25	115	2.19E-10
CL-40C	1.153	1.79	1.93	2.61	0.25	54	4.69E-10
CL-40D	1.155	1.79	1.99	2.61	0.50	102	4.97E-10
CL-40E	1.150	1.79	2.02	2.59	0.50	114	4.43E-10
CL-40F	1.135	1.77	1.90	2.55	0.50	144	3.46E-10
Average			1.99	2.59			3.88E-10

TABLE A.7. Water Retention Data for Concrete. Values at zero matric potential were calculated using weights of supposedly saturated samples.

CL-40A		CL-40B		CL-40C	
Water Potential, -cm	Water Content, cm ³ cm ⁻³	Water Potential, -cm	Water Content, cm ³ cm ⁻³	Water Potential, -cm	Water Content, cm ³ cm ⁻³
0	0.186	0	0.219	0	0.26
2400	0.186	1900	0.219	4100	0.26
10300	0.175	6000	0.213	55000	0.249
30400	0.175	14800	0.207	63100	0.247
43600	0.172	22700	0.204	89700	0.245
55700	0.17	35100	0.198	105500	0.24
61600	0.167	45100	0.196	112700	0.239
86900	0.156	64800	0.194	132600	0.237
90700	0.15	84900	0.188	153000	0.232
105000	0.15	117400	0.182	165300	0.229
128400	0.141	161400	0.173	176200	0.225
166400	0.122	167300	0.154	275700	0.213
205600	0.12	239100	0.143	885100	0.152
885100	0.09	885100	0.112	1164700	0.111
1164700	0.068	1164700	0.087	1468500	0.115
1468500	0.063	1468500	0.081	3077300	0.098
3077300	0.052	3077300	0.068		

CL-40D		CL-40E		CL-40F	
Water Potential, -cm	Water Content, cm ³ cm ⁻³	Water Potential, -cm	Water Content, cm ³ cm ⁻³	Water Potential, -cm	Water Content, cm ³ cm ⁻³
0	0.238	0	0.221	0	0.254
3100	0.238	2700	0.221	3100	0.254
20000	0.227	19700	0.205	44700	0.242
42500	0.222	35100	0.197	65900	0.236
74600	0.217	49100	0.189	71500	0.227
92000	0.214	60700	0.187	94100	0.223
102300	0.211	77600	0.182	102700	0.22
117800	0.209	92200	0.18	117500	0.218
125100	0.207	102500	0.177	132800	0.216
135700	0.206	128300	0.175	202600	0.211
152900	0.198	144100	0.173	277700	0.207
183200	0.192	161900	0.163	885100	0.142
295200	0.188	168100	0.159	1164700	0.112
885100	0.121	211000	0.155	1468500	0.105
1164700	0.098	885100	0.109	3077300	0.087
1468500	0.089	1164700	0.079		
3077300	0.072	1468500	0.079		
		3077300	0.067		

TABLE A.8. Bulk and Particle Density and Saturated Hydraulic Conductivity Data for DSSF Grout Samples from the 14 November 1988 Adiabatic Pilot-Scale Test. Bulk density samples were 10 to 12 cm³. Diameter of conductivity samples was 1.34 cm.

Sample	Maximum Temperature During Curing, °C	Bulk Density, g cm ⁻³	Particle Density, g cm ⁻³	Saturated Conductivity			
				Sample Length, cm	Total Flow, cm ³	Total Time of all Tests, h	Average Value, cm s ⁻¹
A26	85	1.07	-	-	-	-	-
A38	87	1.09	-	-	-	-	-
A73	78	1.06	2.58	-	-	-	-
B06	80	1.15	-	-	-	-	-
B33	94	-	-	-	-	-	-
B52	91	1.09	2.62	-	-	-	-
C16	93	1.12	-	-	-	-	-
C48	99	1.11	-	-	-	-	-
C82	75	1.10	2.63	-	-	-	-
A	-	-	-	2.92	2.1	289	5.52E-9
B	-	-	-	2.95	1.1	257	1.10E-8
C	-	-	-	1.64	6.6	78	5.22E-8
Average		1.10	2.61				2.29E-8

TABLE A.9. Water Retention Data for DSSF Grout (1 bar = 0.1 MPa = 1020 cm).

Sample A26		Sample A38		Sample A73	
Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)
249.41	44.18	229.93	45.69	274.53	45.55
275.36	43.18	273.49	45.01	301.05	44.89
290.83	41.16	280.69	43.34	280.69	43.34
293.02	39.62	292.92	41.91	322.57	41.86
316.83	38.75	317.26	41.06	347.49	41.15
333.50	37.56	335.59	40.01	371.48	40.16
344.91	35.47	344.91	38.40	381.33	38.74
375.01	34.50	380.69	37.40	412.00	37.80
393.46	33.14	390.84	36.26	438.08	36.72
393.97	32.32	399.48	35.54	427.92	36.03
455.56	30.63	455.10	33.94	497.97	34.60
459.16	28.84	455.76	32.35	513.48	32.88
472.16	25.81	418.97	29.79	479.95	26.46
504.09	23.16	453.03	27.50	470.85	28.02
709.95	17.89	634.14	22.01	725.06	22.16
749.84	14.43	679.64	17.27	684.39	18.31
758.30	13.30	709.39	15.20	726.31	16.63
882.43	12.31	779.07	14.36	760.60	15.76
1050.27	10.22	985.74	11.40	960.59	12.75
1249.67	8.20	1251.84	8.99	1151.95	10.10

Sample B06		Sample B33		Sample B52	
Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)
301.96	42.47	249.16	41.97	247.68	44.37
283.90	41.59	251.90	41.27	264.76	43.65
309.93	39.94	389.24	38.93	299.34	41.88
330.52	38.60	290.74	37.21	299.14	40.54
333.16	37.89	313.59	36.12	318.67	39.77
363.78	36.87	362.71	34.79	333.72	38.70
370.61	35.35	350.69	32.73	343.61	37.05
408.29	34.36	388.09	31.17	386.27	36.01
432.55	33.21	411.11	29.56	394.10	34.87
439.25	32.46	416.41	28.66	399.75	34.08
498.47	30.86	496.32	26.46	464.73	32.47
513.48	29.13	515.67	24.56	463.18	30.73
479.95	26.46	507.39	21.88	416.69	28.31
515.21	24.39	596.40	19.25	472.18	25.53
749.09	19.12	839.59	14.26	679.18	19.62
758.88	15.59	908.04	11.44	749.34	15.37
755.07	13.79	842.92	10.97	754.05	14.05
846.92	13.01	926.72	10.47	877.21	12.64

TABLE A.9. (contd)

Sample B06		Sample B33		Sample B52	
Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)	Water Potential, -bars	Water Content, 100 (g g ⁻¹)
1024.26	11.25	1081.36	9.59	1027.32	11.01
1203.06	9.10	1309.42	7.92	1270.74	8.59
Sample C16		Sample C48		Sample C82	
296.41	40.24	234.90	42.00	256.01	44.86
273.77	39.57	240.36	41.11	258.10	44.32
287.74	37.79	284.45	39.18	289.14	42.76
284.16	36.25	285.95	37.55	299.24	41.52
317.15	35.42	294.73	36.67	327.36	40.74
337.46	34.27	329.01	35.48	347.84	39.70
350.93	32.54	333.27	33.55	341.73	38.12
377.20	31.36	372.16	32.34	388.22	37.05
378.34	30.08	387.44	31.34	394.37	35.87
394.23	29.28	375.90	30.16	412.55	35.14
459.71	27.40	442.62	28.14	484.18	33.37
458.45	25.74	463.97	26.13	481.52	31.72
474.58	22.98	458.48	23.12	458.79	29.44
559.41	20.65	550.41	20.42	501.60	26.73
731.20	15.44	746.47	15.36	700.11	21.25
848.06	11.69	856.03	11.81	686.89	17.83
839.57	10.71	840.99	11.04	733.57	16.08
938.70	10.24	920.41	10.44	791.77	14.89
1095.82	9.03	1087.05	9.06	934.32	12.91
1264.66	7.64	1288.62	7.52	1077.55	10.05

TABLE A.10. Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Sandy Sequence of the Hanford Formation. Parameters for location 241-AP are from Smoot et al. (1989). Data for location 88-1 are from Dames and Moore (1988). Parameters for locations 299-E33-38 and MW are from Connelly et al. (1992b).

Well # or Location	Sample	Depth m	θ_s cm ³ cm ⁻³	θ_r cm ³ cm ⁻³	α 1/cm	n	K_s cm s ⁻¹
299-E25-234	5A	1.5	0.4131	0.0188	0.1479	1.3090	5.73E-4
299-E25-234	5B	1.5	0.3367	0.0336	0.0211	1.5364	-
299-E25-234	19A	5.8	0.4700	0.0426	0.1165	1.4816	8.88E-4
299-E25-234	19B	5.8	0.5026	0.0364	0.2728	1.5327	-
299-E25-234	25A	7.6	0.4406	0.0540	0.0473	2.0595	1.80E-3
299-E25-234	25B	7.6	0.5228	0.0345	0.0519	1.3424	-
299-E25-234	25C	7.6	0.5074	0.0282	0.0292	1.3517	-
299-E25-234	25D	7.6	0.5193	0.0000	0.1944	1.3494	-
299-E25-234	29A	8.8	0.4341	0.0000	0.2722	1.1927	2.41E-5
299-E25-234	29B	8.8	0.4387	0.0000	0.1034	1.2240	-
299-E25-234	37A	11.3	0.5114	0.0706	0.0774	1.2924	5.77E-4
299-E25-234	37B	11.3	0.5304	0.0851	0.0894	1.3353	-
299-E25-234	46A	14.0	0.4581	0.0000	0.2923	1.3658	2.99E-4
299-E25-234	46B	14.0	0.3708	0.0000	0.0613	1.4343	-
299-E25-234	54A	16.5	0.4434	0.0278	0.1205	1.4776	1.38E-5
299-E25-234	54B	16.5	0.4543	0.0217	0.1450	1.4421	-
299-E25-234	69A	21.0	0.3722	0.0000	0.3359	1.2658	1.21E-3
299-E25-234	69B	21.0	0.4087	0.0000	0.3553	1.4411	-
299-E25-234	83A	25.3	0.3925	0.0000	0.3198	1.3117	1.78E-4
299-E25-234	83B	25.3	0.3712	0.0011	0.1230	1.3815	-
299-E25-234	99A	30.2	0.3692	0.0000	0.7424	1.2557	2.24E-4
299-E25-234	99B	30.2	0.3774	0.0000	0.4371	1.2961	-
299-E25-234	110A	33.5	0.4293	0.0325	0.1964	1.8193	2.82E-4
299-E25-234	110B	33.5	0.4201	0.0327	0.1991	1.8015	-
299-E25-234	117A	35.7	0.4538	0.0260	0.1114	1.6538	3.63E-3
299-E25-234	117B	35.7	0.3831	0.0012	0.0230	1.5239	-
299-E25-234	126A	38.4	0.3637	0.0000	1.9541	1.2634	1.98E-3
299-E25-234	126B	38.4	0.3747	0.0000	0.8990	1.3152	-
241-AP	1G	-	0.2585	0.0200	0.1008	2.9224	1.24E-3
241-AP	2	-	0.5210	0.0958	0.0309	3.1071	5.97E-4
241-AP	3	-	0.4360	0.0552	0.0494	3.2863	8.10E-4
241-AP	4G	-	0.4086	0.0377	0.0666	2.6751	1.87E-3
241-AP	5	-	0.4280	0.0133	0.0118	1.3945	4.94E-5
88-1	TEST #1	4.8	-	-	-	-	3.01E-2
88-1	TEST #2	9.1	-	-	-	-	5.97E-3
88-1	TEST #3	18.3	-	-	-	-	5.20E-3
299-E33-38	-	15.1	0.2390	0.0000	1.4263	1.2658	5.70E-5
299-E33-38	-	51.0	0.2459	0.0000	0.4612	1.2507	5.00E-4
299-E33-38	-	57.1	0.3714	0.0018	0.0513	1.5057	7.10E-5
MW-10	-	13.7	0.4200	0.0223	0.0640	1.6950	5.31E-3
MW-10	-	26.2	0.4600	0.0253	0.0462	1.9281	1.97E-2

TABLE A.10. (contd)

Well # or Location	Sample	Depth m	θ_s cm ³ cm ⁻³	θ_r cm ³ cm ⁻³	α 1/cm	n	K_s cm s ⁻¹
MW-10	-	32.0	0.3900	0.0271	0.0460	1.6380	1.73E-3
MW-10	-	38.1	0.4400	0.0214	0.0441	1.7647	4.39E-3
MW-10	-	50.3	0.4600	0.0308	0.0351	2.3036	6.63E-3
MW-10	-	59.4	0.3300	0.0487	0.0267	2.3731	2.65E-3
MW-10	-	62.5	0.3600	0.0214	0.0760	1.6255	6.63E-3
MW-10	-	74.7	0.4400	0.0179	0.0630	1.7787	7.39E-3
MW-10	-	80.8	0.4200	0.0169	0.0386	2.1470	2.65E-3
MW-10	-	86.9	0.4700	0.0168	0.0512	2.0848	3.54E-3
MW-5	-	15.2	0.4400	0.0293	0.0810	1.9709	3.53E-2
MW-5	-	21.3	0.4400	0.0485	0.0144	5.4201	1.57E-3
MW-5	-	27.4	0.4400	0.0218	0.0605	2.4414	2.16E-3
MW-5	-	39.6	0.4700	0.0311	0.0184	3.3059	4.42E-2
MW-5	-	51.8	0.4400	0.0281	0.0278	2.7143	3.81E-3
MW-5	-	57.9	0.4300	0.0242	0.0427	3.0699	5.78E-3
MW-5	-	64.0	0.4300	0.0302	0.1533	2.0330	5.42E-3
MW-5	-	70.1	0.4400	0.0243	0.0427	3.1603	5.31E-3
MW-5	-	82.3	0.4400	0.0000	0.1109	1.3428	5.54E-4
MW-8	-	44.2	0.4200	0.0335	0.0186	2.1503	8.86E-4
MW-8	-	56.5	0.4000	0.0367	0.0764	2.0668	7.19E-3
Number of Samples			57	57	57	57	45
Minimum			0.2390	0.0000	0.0118	1.1927	1.38E-5
Maximum			0.5304	0.0960	1.9541	5.4201	4.42E-2
Mean			0.4203	0.0234	0.1943	1.8680	5.48E-3
Variance			3.86E-3	4.63E-4	0.1142	0.5866	8.90E-5
Geom. Mean			0.4152	-	0.0918	1.7562	1.55E-3

TABLE A.11. Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Upper and Lower Gravel Units of the Hanford Formation. All parameters, except those for Well No. 299-E25-234, are from Connelly et al. (1992b).

Well # or Location	Sample ID	Depth m	θ_s $\text{cm}^3 \text{ cm}^{-3}$	θ_r $\text{cm}^3 \text{ cm}^{-3}$	α 1/cm	n	K_s cm s^{-1}
299-E25-234	133A	40.5	0.2732	0.0000	0.0182	1.3095	2.76E-5
299-E25-234	133B	40.5	0.2669	0.0000	0.0321	1.2590	-
299-E33-38	-	1.9	0.5256	0.0000	0.0081	1.7389	2.00E-5
299-E33-38	-	57.9	0.4187	0.0000	0.0027	1.5688	2.10E-6
299-E33-38	-	62.3	0.2905	0.0000	0.0101	1.3652	4.20E-3
299-E33-40	-	14.0	0.3021	0.0000	0.1028	1.2734	6.00E-4
216-B-61A	-	4.1	0.3465	0.0352	0.0061	1.5248	1.80E-3
216-B-61A	-	5.8	0.3253	0.0488	0.0060	1.5120	2.80E-3
216-B-61A	-	7.0	0.3430	0.0000	0.0134	1.2816	4.00E-4
216-B-61A	-	8.8	0.2801	0.0201	0.0609	1.2811	1.80E-5
6-43-41H	-	16.6	0.4510	0.1041	0.0165	1.7894	1.10E-5
6-42-41B	-	25.8	0.3550	0.0301	0.0426	1.3900	5.40E-3
MW-8	-	4.6	0.4400	0.0390	0.0440	3.0387	1.70E-3
MW-10	-	93.0	0.4000	0.0205	0.0427	2.2500	4.42E-3
Number of Samples			14	14	14	14	13
Minimum			0.2669	0.0000	0.0027	1.2590	2.10E-6
Maximum			0.5256	0.1041	0.1028	3.0390	5.40E-3
Mean			0.3584	0.0213	0.0290	1.6130	1.65E-3
Variance			6.12E-3	8.75E-4	7.79E-4	0.2348	3.80E-6
Geom. Mean			0.3509	-	0.0184	1.5600	2.73E-4

TABLE A.12. Water Retention Parameters and Saturated Hydraulic Conductivity Data for the Ringold Formation (undifferentiated). Parameters are from Connelly et al. (1992b).

Well # or Location	Sample ID	Depth m	θ_s $\text{cm}^3 \text{ cm}^{-3}$	θ_r $\text{cm}^3 \text{ cm}^{-3}$	α 1/cm	n	K_s cm s^{-1}
6-42-41B	-	36.1	0.5730	0.0083	0.0132	1.2586	3.00E-8
699-40-40B	-	38.3	0.5680	0.0000	0.0051	1.1732	1.00E-8
699-43-41G	-	50.8	0.5710	0.0941	0.0150	1.4173	1.90E-6
699-43-40	-	39.9	0.3790	0.0387	0.0089	1.4739	1.90E-4
MW-5	-	91.4	0.4000	0.0000	0.0456	1.3661	7.66E-4
Number of Samples			5	5	5	5	5
Minimum			0.3790	0.0000	0.0051	1.1732	1.00E-8
Maximum			0.5730	0.0940	0.0456	1.4739	7.66E-4
Mean			0.4982	0.0283	0.0176	1.3378	1.92E-4
Variance			9.90E-3	1.61E-3	2.61E-4	1.48E-2	1.10E-7
Geom. Mean			0.4897	-	0.0133	1.3333	2.42E-6

TABLE A.13. Water Retention Parameters and Saturated Hydraulic Conductivity Data for Concrete

Sample ID	θ_s cm ³ cm ⁻³	θ_r cm ³ cm ⁻³	α 1/cm	n	K_s cm/s
CL-40A	0.1857	0.0000	1.220E-5	1.3567	3.55E-10
CL-40B	0.2146	0.0000	9.862E-6	1.3409	2.19E-10
CL-40C	0.2593	0.0000	3.826E-6	1.4412	4.69E-10
CL-40D	0.2322	0.0000	4.365E-5	1.4726	4.97E-10
CL-40E	0.2150	0.0000	1.074E-5	1.3396	4.43E-10
CL-40F	0.2480	0.0000	4.669E-6	1.4054	3.46E-10
Number of Samples	6	6	6	6	6
Minimum	0.1857	-	3.826E-6	1.3396	2.19E-10
Maximum	0.2593	-	1.220E-5	1.4726	4.97E-10
Mean	0.2258	-	7.610E-6	1.3927	3.88E-10
Variance	7.012E-4	-	1.389E-11	3.14E-11	1.06E-20
Geom. Mean	0.2245	-	6.822E-6	1.3918	3.75E-10

TABLE A.14. Water Retention Parameters and Saturated Hydraulic Conductivity Data for DSSF Grout

Sample ID	θ_s cm ³ cm ⁻³	θ_r cm ³ cm ⁻³	α 1/cm	n	K_s cm/s
GRT_A26	0.5853	0.0000	1.503E-5	1.5679	5.52E-9
GRT_A38	0.5775	0.0000	9.165E-6	1.6957	-
GRT_A73	0.5891	0.0000	8.804E-6	1.6690	-
GRT_B06	0.5611	0.0000	6.959E-6	1.7719	1.10E-8
GRT_B33	0.5725	0.0000	1.190E-5	1.6304	-
GRT_B52	0.5840	0.0000	1.141E-5	1.6227	-
GRT_C16	0.5741	0.0000	1.574E-5	1.5740	5.22E-8
GRT_C48	0.5779	0.0000	8.946E-6	1.6585	-
GRT_C82	0.5817	0.0000	8.970E-6	1.6565	-
Number of Samples	9	9	9	9	3
Minimum	0.5611	-	6.959E-6	1.5679	5.52E-9
Maximum	0.5891	-	1.574E-5	1.7719	5.22E-8
Mean	0.5781	-	1.077E-5	1.6496	2.29E-8
Variance	6.96E-5	-	9.008E-12	3.884E-3	6.61E-16
Geom. Mean	0.5781	-	1.042E-5	1.6486	1.47E-8

FIGURE A.1. Water Retention and Hydraulic Conductivity Data and Curves for Samples 5A, 5B, 19A, and 19B from Well No. 299-E25-234

FIGURE A.2. Water Retention and Hydraulic Conductivity Data and Curves for Samples 25A, 25B, 25C, and 25D from Well No. 299-E25-234

FIGURE A.3. Water Retention and Hydraulic Conductivity Data and Curves for Samples 29A, 29B, 37A, and 37B from Well No. 299-E25-234

FIGURE A.4. Water Retention and Hydraulic Conductivity Data and Curves for Samples 46A, 46B, 54A, and 54B from Well No. 299-E25-234

FIGURE A.5. Water Retention and Hydraulic Conductivity Data and Curves for Samples 69A, 69B, 83A, and 83B from Well No. 299-E25-234

FIGURE A.6. Water Retention and Hydraulic Conductivity Data and Curves for Samples 99A, 99B, 110A, and 110B from Well No. 299-E25-234

FIGURE A.7. Water Retention and Hydraulic Conductivity Data and Curves for Samples 117A, 117B, 126A, and 126B from Well No. 299-E25-234

FIGURE A.8. Water Retention and Hydraulic Conductivity Data and Curves for Samples 133A and 133B from Well No. 299-E25-234

FIGURE A.9. Water Retention and Hydraulic Conductivity Data and Curves for Backfill Soil

FIGURE A.10. Water Retention and Hydraulic Conductivity Data and Curves for Gravel

FIGURE A.11. Water Retention and Hydraulic Conductivity Data and Curves for RCRA Clay Cap

FIGURE A.12. Water Retention and Hydraulic Conductivity Data and Curves for Concrete Samples CL-40A, CL-40B, CL-40C, and CL-40D

FIGURE A.13. Water Retention and Hydraulic Conductivity Data and Curves for Concrete Samples CL-40E and CL-40F

FIGURE A.14. Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Samples A26, A38, A73, and B06

FIGURE A.15. Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Samples B33, B52, C16, and C48

FIGURE A.16. Water Retention and Hydraulic Conductivity Data and Curves for DSSF Grout Sample C82

WHC-SD-WM-EE-004, Rev. 1

DISTRIBUTION

No. of
Copies

No. of
Copies

OFFSITE

- 12 DOE/Office of Scientific and Technical
Information

C. Frank, EM-50
DOE Office of Technology
Development
Trevion-II
12800 Middlebrook Rd. Germantown,
MD 20874

- 4 DOE Office of Waste Operations
Trevion-II
12800 Middlebrook Rd. Germantown,
MD 20874
ATTN: J. A. Coleman, EM-35
M. W. Frei, EM-34
H. Harmon, EM-32
J. E. Lytle, EM-30

J. C. Haugen
DOE Chicago Operations Office 9800
South Cass Avenue Argonne, IL 60439

F. Bazan
Lawrence Livermore National
Laboratory
University of California
P.O. Box 808
Livermore, CA 94550

- 5 Westinghouse Savannah River
Company
Savannah River Site
Aiken, SC 29808-0001
ATTN: C. A. Langton
R. M. Wallace
E. Wilhite
E. Stevens
M. Hay

M. Fuhrmann
Brookhaven National Laboratory
Upton, NY 11973

T. C. Johnson
Nuclear Regulatory Commission MS-
623SS
Washington, DC 20555

M. McFadden
DOE Albuquerque Operations Office
P.O. Box 5400
Albuquerque, NM 87115

R. M. Neilson, Jr.
EG&G
P.O. Box 1625
Idaho Falls, ID 83415

- 3 Oak Ridge National Laboratory
P.O. Box X
Oak Ridge, TN 37831
ATTN: T. M. Gilliam
E. W. McDaniel
R. D. Spence

E. B. Peacock
Wastech, Inc.
P.O. Box 1213
Oak Ridge, TN 37831-1213

D. M. Smith
University of New Mexico
Chemical and Nuclear
Engineering Department
Albuquerque, NM 87131

No. of
Copies

No. of
Copies

FOREIGN

7 Westinghouse Hanford Company

A. Atkinson
Atomic Energy Research
Establishment
HARWELL
Didcot
Oxfordshire, OX 11 ORA
UNITED KINGDOM

K. C. Burgard
J. L. Epstein
D. W. Hendrickson
F. M. Mann
J. E. Van Beek
J. A. Voogd
G. F. Williamson

L. P. Buckley
Atomic Energy of Canada Ltd. Chalk
River, Ontario KOJ 1JO
CANADA

44 Pacific Northwest Laboratory

P. Cote
Environment Canada
Canada Centre for Inland Waters
Burlington, Ontario LTR 4A6
CANADA

C. R. Allen
M. P. Bergeron
K. A. Blanchard
C. R. Cole
R. M. Ecker
M. J. Fayer (5)
A. R. Felmy
H. D. Freeman
M. D. Freshley
G. W. Gee
M. J. Graham
P. C. Hays
P. R. Heller
P. M. Irving
C. T. Kincaid
D. K. Kreid
R. J. Lenhard
R. O. Lokken
P. D. Meyer
M. I. McKinley
W. E. Nichols
K. R. Roberson
M. L. Rockhold (5)
W. A. Ross
P. A. Scott
J. R. Serne
R. L. Skaggs
C. S. Sloan
J. H. Westsik, Jr.
G. A. Whyatt
Publishing Coordination
Technical Report Files (5)

R. Dayal
Ontario Hydro
800 Kipling Ave.
Toronto, Ontario M8Z 5S4
CANADA

C. L. Farmer
Atomic Energy Establishment
WINFRITH
Dorchester, Dorset DT2 8DH
UNITED KINGDOM

ONSITE

3 DOE Richland Operations Office

K. W. Bracken
L. A. Huffman
G. L. Sanders

Appendix K

Status Report on Ionic Diffusion Through Asphalt

Draft Letter Report for Westinghouse Hanford Company

STATUS REPORT ON IONIC DIFFUSION THROUGH ASPHALT

P. F. C. Martin
R. J. Serne
V. L. LeGore
C. W. Lindenmeier

November 1992

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland Washington

LIMITED DISTRIBUTION NOTICE

This document copy, since it is transmitted in advance of patent clearance, is made available in confidence solely for use in performance of work under contracts with the U.S. Department of Energy. This document is not to be published nor its contents otherwise disseminated or used for purposes other than specified above before patent approval for such release or use has been secured, upon request, from Patent Services, Pacific Northwest Laboratory, Richland, Washington 99352.

SUMMARY

Containment structures for grouted wastes produced at the Hanford site incorporate an asphalt/aggregate barrier that surrounds the primary vault of reinforced concrete. The purpose of the asphalt/aggregate barrier is to retard the release of contaminants to the environment, as modeled in performance assessment activities, to acceptably low levels. Tests to determine diffusion rates of ionic contaminants were begun in FY91 and continued in FY92. The continuing experiments were American Nuclear Society (ANS) 16.1 leach tests of asphalt/aggregate composite samples spiked with radionuclides and diffusion analyses of contaminants into asphalt coupons immersed in contaminant spiked solutions. From these tests the diffusion of organic complexed cobalt ($^{60}\text{Co}^{2+}$ -EDTA), cesium ($^{137}\text{Cs}^{+}$), iodide ($^{125}\text{I}^{-}$), nitrate (NO_3^{-}), and pertechnetate ($^{99}\text{TcO}_4^{-}$) were assessed.

Leach tests have yielded effective diffusivities below the baseline value of $1 \times 10^{-10} \text{ cm}^2/\text{sec}$ used in performance assessment (PA) calculations. Bulk diffusivities for NO_3^{-} and $^{99}\text{TcO}_4^{-}$, adjusted to a consistent basis for PA calculations, yield diffusivities that are approximately 60% of the PA baseline value for NO_3^{-} and approximately 25% of the baseline value for $^{99}\text{TcO}_4^{-}$. The other bulk diffusivities are well below the PA baseline value. However, by drying the contaminants onto the aggregate before coating with asphalt it is possible that results are biased low by allowing adsorption on the aggregate to retard release of some contaminants.

Immersion tests on asphalt alone (no aggregate in sample) have yielded diffusion coefficients that are well below the PA calculation baseline. These tests involved determining contaminant concentrations in microtomed slices taken from asphalt "coupons" exposed on one surface to contaminant-spiked solutions to yield a concentration profile. These concentrations were then transformed using the "probit" technique to calculate the diffusivities of the contaminants.

Other activities included the development and fabrication of asphalt/aggregate composite membranes and the manufacture of fourteen half-cell diffusion test assemblies from an improved design. These

half-cells will be used in FY93 to perform further diffusion measurements. The half-cell tests are important because 1) the half-cell membranes are made without incorporated contaminants, 2) the membranes are fabricated using methods representative of those used in construction of the asphalt/aggregate barrier, 3) the membranes incorporate all materials used in the actual barrier, and 4) the half-cells simulate the two diffusion interfaces of the grout disposal system, namely, the vault-asphalt interface and the asphalt-vadose sediment pore water interface.

INTRODUCTION

At Hanford, the disposal system for grout-solidified tank wastes includes an engineered barrier constructed of an asphalt/aggregate mix measuring approximately one meter thick that surrounds the entire concrete grout containment vault and the vault's leachate collection system. The purpose of this asphalt/aggregate barrier is to greatly impede the diffusion of water-soluble contaminants by interposing a hydrophobic material that breaks contact between dissolved contaminants in the waste form and the surrounding soil and soil pore water. The DSSF grout performance assessment (PA) calculations show that the values chosen for contaminant diffusion through the diffusion barrier are key to determining whether the proposed grout disposal system will minimize long-term risks to acceptable levels.

The values for the diffusion coefficients chosen in PA calculations were gleaned from generic literature. Diffusion of water solutes through asphalt/aggregate are expected to be very small (e.g., D_e values $<10^{-10}$ cm²/s) such that classical methods to determine diffusion coefficients would require testing activities to span several years. For example, Daiev and Vassilev (1985) found ⁹⁰Sr diffusion coefficients through pure bitumen to be 1.5 to 3.3 x 10⁻¹² cm²/s in tests that took 6 to 12 years to yield data. The penetration depth of ⁹⁰Sr was only 0.06 cm and 0.09 cm after 6 and 12 years, respectively.

The purpose of tests conducted in FY91-92 were to determine effective diffusion coefficients for representative contaminants found in DSSF grout through asphalt and the asphalt/aggregate mix used to construct the diffusion barrier. The tests conducted provide Hanford-Site specific data that will verify whether values chosen in the PA calculations are appropriately conservative. That is, our tests experimentally addressed whether the effective diffusion coefficients of contaminants through solid asphalt and asphalt/aggregate mix are less than 1 x 10⁻¹⁰ cm²/s. Because each contaminant could have a distinctly different effective diffusion coefficient, we have studied several important contaminants. The experimental methods being used include the ANS 16.1 leach method, an immersion method and a half-cell method.

METHODS

LEACH TEST METHODS

Selection of radionuclides and ionic species for use in evaluating diffusivity through asphalt were driven by the chemical composition of the waste, a knowledge of which chemical species are most problematic in performance assessment calculations, and also because of practical considerations of experimental detection. Nitrate, $^{99}\text{TcO}_4^-$, and $^{129}\text{I}^-$ are mobile contaminants within DSSF grout that constitute significant dose and contamination hazards in PA calculations. $^{125}\text{I}^-$ was substituted for $^{129}\text{I}^-$ because it is a more convenient isotope to use in testing. $^{137}\text{Cs}^+$ was chosen to represent other water-soluble contaminants that readily diffuse through both grout and concrete. $^{137}\text{Cs}^+$ is also an ideal tracer because it has a long half-life and, as a strong gamma emitter, is easily detectable. Cobalt-60 was used because it forms a strong organic complex with chelators such as EDTA. The behavior of ^{60}Co -EDTA complex should make clear if diffusion is enhanced by organic chelation through increased chelated-contaminant solubility in asphalt.

Table 1 shows the contaminants incorporated into the asphalt/aggregate leach test samples. The samples used in these leach tests consisted of cylinders made from asphalt/aggregate into which the contaminants had been incorporated using the following technique. Contaminants were dried onto the aggregate along with the hydrated lime that is used to enhance the adhesion of asphalt to the aggregate. The contaminant-spiked aggregate was then heated to barrier construction specifications, mixed with molten asphalt, and compacted into cylindrical molds to a void content of less than 4 vol%. Before starting, duplicate samples of asphalt/aggregate (samples 1 through 8 in Table 1) were "cured" in their molds at room temperature or at 90°C for several days. To address precision, triplicate samples 9 through 11 were cured at room temperature.

TABLE 1. Leach Test Sample Contaminants

<u>Sample</u>	<u>Contaminants</u>
1, 2, 3, 4	NO_3^- and $^{125}\text{I}^-$
5, 6, 7, 8	NO_3^- and $^{99}\text{TcO}_4^-$
9, 10, 11	$^{137}\text{Cs}^+$ and $^{60}\text{Co}^{2+}$ -EDTA
12, 13, 14	none

Eleven asphalt/aggregate specimens (4.0-cm diameter by 5.1 to 5.7-cm long) are being tested at room temperature. The leach tests employ the ANS 16.1 leaching procedure in which solids of known geometric surface area are immersed in a known quantity of leachate. The samples are periodically immersed in fresh leachant, and the previous leachate is analyzed for concentration of the contaminants. The leachate change is made to ensure that the concentration gradient driving diffusion is as large as practicable. Use of this method also assumes that the asphalt does not react significantly with the leachant, the surface area available for leaching does not change, and that contaminants are not released from the sample by any other time-dependent mechanisms. Meeting these assumptions permits the use of the following equation to calculate a diffusion coefficient (Godbee et al. 1980):

$$D_e = \frac{\pi}{4} \left(\frac{\sum a_n}{A_0} \right)^2 \left(\frac{V}{S} \right)^2 \left(\frac{1}{t} \right) \quad (1)$$

where D_e = bulk diffusivity (cm^2/s)

a_n = amount of contaminant released in the n^{th} water exchange
(radionuclide decay corrected to activity at test start)

A_0 = initial inventory of contaminant in sample

V = geometric volume of sample (cm^3)

S = geometric surface area of sample (cm^2)

t = total time of leaching (s).

IMMERSION TEST METHODS

The immersion method employed "coupons" of asphalt contained within Teflon® polytetrafluoroethylene (PTFE) molds. A total of 34 samples were prepared and were immersed in one of two 4 M NaNO₃ solutions. One solution was spiked with ¹³⁷Cs⁺, and the other with ⁹⁹TcO₄⁻. The coupons are approximately 1.3-cm thick x 3.2-cm square. Because asphalt was exposed to the immersion fluid on only one surface, the contaminants could diffuse into the sample in one direction only. Surface PTFE exposed to the immersion solution was removed to approximately half of its 1/8 in. thickness before microtoming asphalt coupons to measure diffusion. PTFE immediately under the exposed surface was assayed for radionuclide activity to ensure that it had served as a barrier to diffusion of contaminants as intended. No net measurable activity was detected below the surface-contaminated slices of the PTFE coupon molds implying that there was no detectable diffusion of contaminants through the PTFE into the asphalt.

Following 263 days of immersion, two coupon samples were removed from each of the immersion baths and rinsed with deionized water. The asphalt coupons were then carefully sectioned using a microtome set to cut a nominal thickness of 20 μm. Any remaining PTFE was pulled from the coupon before the sections were placed into separate tared vials for radionuclide assay or further treatment, such as extraction or dissolution.

Each of the thin sections thus obtained were analyzed for concentration of the contaminant. ¹³⁷Cs was analyzed by direct gamma counting. Asphalt slices from the same nominal depths of two coupons were composited to increase the activity for improved counting.

Nitrate concentrations were obtained from the microtomed asphalt slices following ¹³⁷Cs assay by extraction using water vapor, as follows. A small aliquot of deionized water was added to the vials which were then tightly capped and placed in a constant-temperature oven operating at 75°C. After two weeks the vials were cooled and the resulting solutions were analyzed for NO₃⁻ using Ion Chromatography (IC).

Concentrations of ^{99}Tc were determined by scintillation counting. Microtomed slices from asphalt coupons, immersed in a $200\ \mu\text{Ci/L } ^{99}\text{Tc } 4\ \text{M NaNO}_3$ solution, were weighed before being dissolved in aliquots of scintillation cocktail. The scintillation cocktail completely dissolved the asphalt but the solutions were opaque. Aliquots of the resulting opaque solutions were then diluted with more scintillation cocktail to give solutions of equal asphalt concentration so that the reduction in counting efficiency (in this case, light transmission) would be the same for each sample.

The effective diffusion coefficients were determined using probit methods (a mathematical reduction scheme) described in Phillips and Brown (1964), and Brown et al. (1968, 1969). Using the analytical data, the ratios of contaminant concentration, present in each of the asphalt thin sections, over the initial concentration driving diffusion into the coupon, were calculated (C/C_0). These normalized concentration values were then transformed into probits by interpolating corresponding values from a table in Probit Analysis (Finney, 1971). The mathematical manipulations require plotting the probit of normalized concentration, C/C_0 , at a given sampling time, versus distance from the interface. A least squares linear regression was performed on the values of probit number versus median distance from the surface. The diffusion coefficient (D) is related to the square of the slope by the following formula:

$$D = \frac{1}{2m^2t} \cdot \text{cm}^2/\text{s} \quad (2)$$

where m is the slope of the regression line and t is the total time of diffusion (exposure) in seconds.

Use of this mathematical approach assumes that the concentration of the diffusing substance remains constant at the interface (asphalt surface-solution boundary) and that the asphalt specimen's dimensions are semi-infinite (much larger than the distance of penetration of diffusing substances). Data have indicated that both assumptions are valid for these tests.

The technique for these probit tests was based on diffusion from a uniformly contaminated soil sample in contact with an uncontaminated soil sample. After a suitable period, the soil diffusion test produces data distributed in a normal sigmoid curve with its center at the interface between the two soil samples. The test is intended to be semi-infinite in both directions from the interface, consequently, a) on the contaminated sample side, contaminant concentrations increase to the C_0 concentration with increasing distance from the interface (depleting contaminant source), b) on the initially uncontaminated side, contaminant concentrations decrease to zero with increasing distance from the interface, and c) contaminant concentration at the interface will equal 50% of the C_0 . In our coupon tests diffusion is semi-infinite in only one direction so we must adjust our data analysis scheme as follows.

When applied to the immersion of asphalt coupons immersed in a contaminant-doped fluid, the diffusion conditions are approximated by a constant (non-depleting) contaminant source diffusing into a semi-infinite volume of asphalt. The concentration profile developed with these boundary conditions is one-half the normal sigmoid curve. To apply the probit transformation to the data generated in the asphalt test, the contaminant concentrations are converted to percents (normalized) using C_0' where $C_0' = C_0 \times 2$. C_0' represents the initial concentration that would have been needed to develop the concentration profile from a test set up with boundary conditions of the soil diffusion test that produces conditions (b) and (c) above. After conversion of the data from microtomed slices to probits using C_0' , the diffusivity is then calculated as described in equation 2.

RESULTS

LEACH TEST RESULTS

Leach tests of radioactively spiked asphalt/aggregate samples have been underway since late April 1991. The latest leachant change-out occurred at an elapsed time of 330 days. Data from leachate analysis for these samples are presented in Table 2.

The data in Table 2 clearly show that different contaminants are released from the asphalt/aggregate samples at different rates, with NO_3^- and $^{99}\text{TcO}_4^-$ leaching fastest and ^{137}Cs slowest. Those samples that were cured for several days at 90°C leach at a slower rate than those that were cured at room temperature. It is likely that hot curing produced a better surface film of asphalt around the aggregate, and therefore, produced a sample that released its contaminants more slowly. The incremental leach rates have dropped since the start of the leach test, which may have been the result of an initial release of contaminants through small surface imperfections in the sample. At later intervals the leach rates dropped because contaminant sources near these imperfections had become relatively depleted.

The bulk diffusion coefficients calculated from the laboratory tests assume that the entire volume of the specimen can promote diffusion. However, the PA conceptual model and computer codes assume that diffusion occurs only in the asphalt phase—that is, the aggregate and any air voids cannot support diffusion. To get the same flux of contaminants through the asphalt/aggregate barrier, as measured in the ANS 16.1 leach tests, the leach test-derived values are multiplied by the fractional volume of diffusion-supporting asphalt. Diffusivities are first calculated using a contaminant-concentration driving force defined in the entire asphalt/aggregate mix, this is then adjusted to a driving force based on concentrations that would be found in the asphalt phase. This places the diffusivities on a consistent basis. For this

TABLE 2. Bulk Effective Diffusion Coefficients (cm²/s) for Contaminants of Asphalt-Coated Aggregate Samples from ANS 16.1 Leach Tests

Contaminant	Cured	D _e (incremental) (224-330 days)	D _e (cumulative) (through 330 days)
125I ⁻ (a)	20°C	8.1 ± 5.1 x 10 ⁻¹²	2.8 ± 1.0 x 10 ⁻¹¹
	90°C	3.2 ± 0.7 x 10 ⁻¹²	1.4 ± 0.4 x 10 ⁻¹¹
99TcO ₄ ⁻	20°C	3.6 ± 0.6 x 10 ⁻¹¹	1.4 ± 0.2 x 10 ⁻¹⁰
			2.3 ± 0.2 x 10 ⁻¹¹ (b)
	90°C	4.9 ± 0.1 x 10 ⁻¹¹	1.2 ± 0.1 x 10 ⁻¹⁰
			1.9 ± 0.2 x 10 ⁻¹¹ (b)
137Cs ⁺	20°C	< 3 x 10 ⁻¹⁴	< 5 x 10 ⁻¹⁴
60Co ²⁺ -EDTA	20°C	1.2 ± 0.3 x 10 ⁻¹¹	8.3 ± 0.9 x 10 ⁻¹²
NO ₃ ⁻ (c)	20°C	1.5 ± 0.2 x 10 ⁻¹⁰	3.5 ± 0.2 x 10 ⁻¹⁰
			5.7 ± 0.2 x 10 ⁻¹¹ (b)
	90°C	1.8 ± 0.1 x 10 ⁻¹⁰	2.7 ± 0.1 x 10 ⁻¹⁰
			4.4 ± 0.1 x 10 ⁻¹¹ (b)

- (a) I⁻ incremental period 56-98 days, cumulative period 98 days
 (b) values are adjusted by 0.162 (explained in text)
 (c) nitrate values are an average of two samples

barrier, the modelers take the test-derived values and multiply by 0.162, the volume fraction of asphalt in the mix¹. This adjustment means that a reported diffusivity value (Table 2) above 6.17 x 10⁻¹⁰ cm²/s (1 x 10⁻¹⁰/0.162) would require that PA base conditions be reevaluated. Currently, the highest cumulative diffusion coefficient for NO₃⁻ is approximately 60% of this value, and the values for 99TcO₄⁻ are approximately 25% of this value.

The effective diffusion coefficient for I⁻ is approximately ten times lower than that for TcO₄⁻. Past studies have demonstrated little

¹ This has the simultaneous effect of requiring placement of all of the contaminant in the smaller asphalt volume (capable of promoting diffusion) so that contaminant concentrations at the vault/diffusion barrier interface would be 6.25 (1/0.16) times as large as the values in the the bulk homogeneous sample as employed in the leach test.

tendency for either TcO_4^- or I^- to adsorb onto Hanford sediments (in this case, local aggregate). Because adsorption of I^- on the aggregate is unlikely it is unclear what is causing the difference in diffusivities. General literature on iodide does suggest that organic rich sediments can bind iodine strongly. Researchers speculate that iodide (I^-) gets converted to iodine (I_2) in the presence of organic matter. The iodine is then bound strongly. Asphalt, being predominately organic, might be converting iodide to iodine.

The ^{60}Co -EDTA complex and ^{137}Cs are retained quite well compared to $^{99}\text{TcO}_4^-$ and NO_3^- . It is concluded that EDTA-complexed contaminants are not mobilized in asphalt to an extent that would cause concern. It is believed that ^{137}Cs retention is most likely a result of adsorption on the aggregate. Cesium release may have been greater if the contaminant had been incorporated in the sample when coating aggregate with asphalt. Despite the fact that the asphalt/aggregate specimens are showing signs of surface changes in the de-ionized water leachant solution there is no indication of an increase in the release of contaminants.

The leachates from these leach tests can be easily monitored for ^{60}Co -EDTA, ^{137}Cs , NO_3^- , and $^{99}\text{TcO}_4^-$ with minimal resources on a yearly basis. Therefore, these experiments should be monitored for the duration of the research effort on ionic diffusion through asphalt to observe if the phenomena described above continue.

IMMERSION TEST RESULTS

The following figures depict data from the immersion of asphalt coupons. In each figure the filled symbols represent values obtained by using a C_0 based on contaminant concentrations from the first slices microtomed from the asphalt coupons. The empty symbols represent values based on a C_0 using the contaminant concentrations of the immersion solutions. In addition, a least-squares line was fit to each of the data sets. The data and the line fits are discussed below.

Probit plots for $^{137}\text{Cs}^+$ (Figure 1) and NO_3^- (Figure 2) were calculated for asphalt coupons removed from a $100\ \mu\text{Ci/L}$ ^{137}Cs -doped $4.0\ \text{M}$ NaNO_3 immersion bath following 263 days of exposure.

FIGURE 1. ^{137}Cs Probit from Asphalt Coupon Immersion Test

FIGURE 2. NO_3^- Probit from Asphalt Coupon Immersion Test

Technetium probit data (Figure 3) were determined by scintillation counting of dissolved asphalt slices from coupons immersed in a 4 M NaNO_3 solution containing 200 $\mu\text{Ci/L}$ $^{99}\text{TcO}_4^-$. Initially opaque solutions were diluted so that the concentration of asphalt in each vial was identical. In this way reduction of counting efficiency (in this case, light transmission) would be the same for each sample. The intermediate preparatory steps, required to perform these radioassays, resulted in the increased scatter in the probit plot.

Interpretation of the data shown in Figures 1 through 3 requires a knowledge of the solubility of the contaminant in asphalt. Because the solubility data were unavailable when these experiments were begun, the data were evaluated using the following two cases; each making different assumptions about the solubility of the contaminants.

FIGURE 3. $^{99}\text{TcO}_4^-$ Probit from Asphalt Coupon Immersion Test

Case I: Initial concentration (C_0) of the contaminant, driving diffusion into the asphalt coupon, equals the concentration of the contaminant in the immersion solution. This case assumes that the contaminant is readily soluble in asphalt, at least at the concentrations present in solutions. (In these experiments this possibility is only likely for radionuclides, not nitrate, because the radionuclides are present in very small quantities). When this case is applied to the immersion test data the resulting normalized concentrations are relatively small because the C_0 chosen is large and the contaminant concentrations in the slices do not approach the C_0 value.

Case II: The solubility and thus the C_0 of the contaminant in the first slice from the asphalt coupon approximately equals the concentration found in that first slice. Alternately, contaminant

solubility in the asphalt has reached equilibrium at the concentration present in the first slice, and it is this concentration, in this layer of asphalt, that is driving diffusion into the bulk of the asphalt sample. This concentration represents a solubility significantly lower than the contaminant concentration in the immersion solution. A linear regression of the data yields a relatively larger slope (more negative). A larger slope yields a smaller effective diffusion coefficient for the contaminant. This is because a steeper slope indicates a relatively rapid decrease in concentration between slices from the coupon, therefore, diffusion of contaminant into the sample is proceeding slowly. Compared to linear regressions of case II probit values, case I probits yield smaller slopes and thereby yield greater diffusivities because contaminant concentrations do not fall off as rapidly. Table 3 shows the diffusivities calculated for cases I and II. These diffusivities are well below the maximum diffusivity of $1 \times 10^{-10} \text{ cm}^2/\text{s}$ used in current baseline performance assessment calculations.

There are 13 asphalt coupons remaining in the $^{99}\text{TcO}_4^-$ -doped immersion bath and 6 asphalt coupons remaining in the $^{137}\text{Cs}^+$ -doped immersion bath. These immersion tests require minimal attention and can be continued through FY95 with a small investment of resources to remove a pair of samples from each of the two baths for microtoming and radioassay. Examination of these samples each fiscal year will improve precision of the contaminant-specific diffusivities because the concentration profiles will develop further into the sample improving the accuracy of the probit transformation.

TABLE 3. Effective Diffusion Coefficients, 263-day Exposure (cm^2/s)

<u>Contaminant</u>	<u>Case I Based on Solution Conc.</u>	<u>Case II Based on Conc. in First Slice</u>
$^{137}\text{Cs}^+$	1.7×10^{-12}	6.1×10^{-13}
NO_3^-	4.7×10^{-12}	5.1×10^{-13}
$^{99}\text{TcO}_4^-$	4.2×10^{-11}	1.5×10^{-11}

ASPHALT/AGGREGATE "MEMBRANE" DEVELOPMENT

The diffusivities calculated from the ANS 16.1 leach tests may be problematic insofar as the contaminants were incorporated into the sample by drying them onto the aggregate with the lime coating. If this method of contaminant incorporation is responsible for the retention of contaminants, then the diffusivities calculated are too low. This implies that the samples may not reasonably represent the behavior of the actual diffusion barrier. The results may also be problematic because the leach rates have been declining with time. This decrease is perhaps partly attributable to the initial release of contaminants from contaminant sources near defects in the surface of the specimens that have been depleted as the experiment progresses. This implies that an important criterium for assessing the validity of the method has not been met, namely "release of contaminants by other time-dependent mechanism does not occur".

The diffusivities calculated from immersion tests of asphalt-only coupons may be problematic in that they do not incorporate aggregate and because they only simulate one interface present in the waste disposal system. Because the contaminant diffuses only into asphalt and not back out an important component in the behavior of the system may be lacking. This is important because certain contaminants, such as $^{99}\text{TcO}_4^-$ and organic-complexed contaminants may actually concentrate in the asphalt and thereby not diffuse as rapidly from the system.

Half-cell diffusion tests do not share these same problematic aspects. Contaminants will not be incorporated into the membrane so artifacts of sample preparation will not be important. In addition the half-cell membranes do incorporate aggregate and are fabricated using techniques that simulate the field construction methods. Most importantly half-cell test assemblies simulate the two diffusion interfaces of the waste disposal system, namely the waste form-asphalt interface and the asphalt-vadose sediment pore water interface.

Half-cell diffusion experiments, conducted in FY91, employed a 0.05 cm thick asphalt-only membrane as a partition between the two half cells. These membranes proved inadequate and failed before definitive

data could be obtained. In FY93, membranes will be composed of asphalt mixed with aggregate compacted to a void content of less than 4 vol%. Because of time constraints, the membrane must be sufficiently thin to allow detection of contaminant diffusion within months. However, the membrane must also be sufficiently thick, and incorporate all materials designed into the barrier, so that the test articles are reasonably representative of the diffusion barrier. The compromise reached for the tests planned for FY93 incorporate aggregate from which the two largest size fractions have been removed. The maximum nominal size aggregate passed a U.S. Standard No. 4 sieve (4.75 mm) and equals 1/2 or less of the nominal membrane thickness of 1.5 to 2.0 cm. Using this size fraction as a maximum resulted in removing 30 wt% of the specified aggregate mix (WHC construction specification B-714-C2, rev. 1).

New weight percents of asphalt and lime were calculated based on the increased surface area resulting from the elimination of the larger aggregate particles. Aggregate was obtained from the construction contractor and separated by sieving into the specified size fractions. These size fractions were further separated into size fractions required by the Asphalt Institute's (1989) Hveem method for laboratory design of pavement mixtures. The Hveem method uses an aggregate surface area calculation to provide a recommended starting point for optimizing asphalt content in a paving mix. Surface area is calculated by summing the weight fraction of all the individual aggregate size ranges multiplied by their associated surface area factors. The method was used to calculate the change in surface area caused by eliminating the larger particle sizes from the half-cell membrane asphalt/aggregate mix. This nominal change was then used to calculate increased vol% asphalt and increased wt% lime by multiplying construction specification asphalt and lime contents by the same nominal change. The asphalt and lime-coated aggregate were heated to the temperatures specified in the construction specification, mixed, and compacted into 4 in. lengths of stainless steel pipe using ASTM (1990) procedures. All compacted samples had less than three percent air voids (diffusion barrier specification stipulates less than four percent air voids).

Test membranes, developed and fabricated in FY92, include a small band of the stainless steel mold into which the asphalt mix was compacted. This metal ring provides a non-deformable seal between the asphalt-aggregate membrane and the half-cell apparatus. Compacted asphalt/aggregate samples were sectioned into membranes approximately 1.5 to 2.0 cm thick using an abrasive cutting saw with water coolant. The membranes were then ground flat and parallel using a water-cooled surface grinder. In FY93 bubble leak tests will be conducted on the membranes to detect any gross surface-connected porosity. A composite membrane may incorporate surface-connected porosity due to void content and/or aggregate particles that are incompletely coated with asphalt. After leak testing, the aggregate exposed during sawing will be dried and the surfaces of the membranes sealed with a ≤ 0.05 -mm thick coating of asphalt.

The design for the half-cell apparatus was modified to incorporate the membrane with the stainless steel outer ring described above. Rubber (EPDM) O-rings provide the seal between the membrane and the half cells. In addition, an expanded stainless steel support has been added to restrict "cold-flow" sagging of the membrane and permit testing of the membrane at 55°C.

It is anticipated that several months will pass before breakthrough of contaminants can be detected in the "cold" (non-radiotraced) reservoir because contaminants must diffuse through the entire uncontaminated membrane. When buildup of the contaminant has been reliably detected and assayed, the solution in the cold reservoir will be entirely emptied and fresh solution will be added. Buildup of the contaminant must be kept to a minimum because of the assumption of an unchanging concentration-derived driving force in the mathematical model used to calculate the diffusivities (Crank, 1975). Elapsed time for subsequent analyses will be shorter because the membrane will have been "charged" with contaminant. The elapsed time between breakthrough, when the cold solution is replaced, and the time when the contaminant has again built up to a reliably detectable concentration, will yield the data necessary to calculate diffusivities.

CONCLUSIONS

Leach tests of asphalt aggregate samples continue to yield bulk effective diffusivities below the maximum diffusivity ($1 \times 10^{-10} \text{ cm}^2/\text{s}$) assumed in PA baseline calculations (Table 2). Even though the cumulative diffusivities for NO_3^- and $^{99}\text{TcO}_4^-$ exceed $1 \times 10^{-10} \text{ cm}^2/\text{s}$, the PA conceptual model multiplies bulk diffusivities by 0.162 to make the values consistent with a driving force confined to the asphalt phase. Using this factor the diffusivity values for NO_3^- are approximately 60% of the adjusted maximum and $^{99}\text{TcO}_4^-$ diffusivity values are approximately 25% of the adjusted maximum.

Other diffusivities calculated from ANS 16.1 leach tests were well below PA baseline values. In addition, it has been observed that the effective diffusion coefficient for I^- is approximately ten times lower than that for TcO_4^- . Past studies have demonstrated little tendency for either TcO_4^- or I^- to adsorb onto Hanford sediments (in this case, local aggregate). Because adsorption on the aggregate is unlikely it is, therefore, unclear what is causing the difference in diffusivities. An observation from technical soils literature that organic rich sediments can convert iodide (I^-) to iodine (I_2) that is then strongly bound to the soil, may be occurring because asphalt is an organic material.

The $^{60}\text{Co}^{2+}$ -EDTA complex and $^{137}\text{Cs}^+$ are retained quite well compared to $^{99}\text{TcO}_4^-$ and NO_3^- . It is also concluded that EDTA-complexed contaminants are not mobilized in asphalt to an extent that would cause concern. It is believed that ^{137}Cs retention is most likely a result of adsorption on the aggregate: Cesium release may have been greater if the contaminant had been incorporated into the test sample during aggregate coating with asphalt.

Immersion tests on asphalt-only coupons yielded diffusivities well below PA baseline values. Diffusivities of $^{137}\text{Cs}^+$, $^{99}\text{TcO}_4^-$, and NO_3^- were calculated using two probit transformation approaches: The first approach used a driving force defined by contaminant concentrations in the immersion solutions (case I), and the second approach used a driving force defined by smaller concentrations found in the top-most slices of asphalt from the coupons (case II).

Half-cell tests employing a composite asphalt/aggregate membrane are necessary to resolve questions about whether the retention of some contaminants in leach tests are artifacts of sample preparation. Results from half-cell tests will also be the most straightforward to interpret because 1) the half-cell membranes are made without incorporated contaminants, 2) the membranes are fabricated using methods representative of those used in construction, 3) the membranes incorporate all materials used in the actual barrier, and most importantly, 4) the half-cells simulate the two diffusion interfaces of the grout disposal system, namely, the vault-asphalt interface and the asphalt-vadose sediment pore water interface.

REFERENCES

- ANS. 1986. Measurement of the Leachability of Solidified Low-Level Radioactive Wastes by a Short Term Test Procedure. ANSI/ANS16.1, American Nuclear Society, La Grange Park, Illinois.
- ASTM. 1990. American Society for Testing Materials. 1990 Annual Book of ASTM Standards. Vol. 04.03, Road and Paving Materials; Pavement Management Technologies. Philadelphia, Pennsylvania.
 D1559-82, "Standard Test Method for Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus";
 D2041-90, "Standard Test Method for Theoretical Maximum Specific Gravity of Bituminous Paving Mixtures";
 D2726-89, "Standard Test Method for Bulk Specific Gravity and Density of Compacted Bituminous Mixtures Using Saturated Surface-Dry Specimens";
 D3203-88, "Standard Test Method for Percent Air Voids in Compacted Dense and Open Bituminous Paving Mixtures".
- Asphalt Institute. 1989. (Hveem Surface Area). "Chapter 3.2, Aggregate Analysis" and "Chapter 4.3, Asphalt Hot Mix Design Methods", The Asphalt Handbook. MS-4, Asphalt Institute, College Park, Maryland. pp. 100-107, pp. 149-150.
- Brown, D. A., J. E. Dunn and B. D. Fuqua. 1969. "Multiple-Ion Diffusion - I. Techniques for Measuring and Calculating Apparent Self-Diffusion Coefficients in Heteroionic Systems," Clay and Clay Minerals. 17:271-277.
- Brown, D. A., R. E. Phillips, L. D. Ashlock and B. D. Fuqua. 1968. "Effect of Al^{3+} and H^+ upon the Simultaneous Diffusion of ^{85}Sr and ^{86}Rb in Kaolinite Clay," Clay and Clay Minerals. 16:137-146.
- Crank, J. 1975. The Mathematics of Diffusion - Second Edition, Clarendon Press, Oxford, England.
- Daiev, Ch. T., and G. P. Vassilev. 1985. "On the Diffusion of ^{90}Sr From Radioactive Wastes Bitumenized by the Mould Method," J. of Nucl. Mat. 127:132-136.
- Finney, D. J. 1971. Probit Analysis. 3rd Edition. Cambridge University Press, Cambridge, England. pp. 283-287.
- Godbee, H. W., E. L. Compere, D. S. Joy, A. H. Kibbey, J. G. Moore, C. W. Nestor, Jr., O. U. Anders and R. M. Neilson, Jr. 1980. "Application of Mass Transport Theory to the Leaching of Radionuclides From Waste Solids," Nucl. Chem. Waste Manage. 1:29-35.
- Phillips, R. E. and D. A. Brown. 1964. "Ion Diffusion: II. Comparison of Apparent Self and Counter Diffusion Coefficients," Soil Sci. Soc. of Am. Proceed. 28:758-763.

APPENDIX

PROBIT DATA FROM IMMERSION TESTS

TABLE A1. Probit Data for Diffusivity Calculations

<u>Slice</u>	<u>Mass</u> <u>g</u>	<u>Median</u> <u>Depth, cm</u>	<u>Activity</u> <u>$\mu\text{Ci/g}$</u>	$\bar{C}/C_0$ $\times 100$ <u>Case I</u>	<u>Probit</u> <u>Case I</u>	$\bar{C}/C_0$ $\times 100$ <u>Case II</u>	<u>Probit</u> <u>Case II</u>
$^{137}\text{Cs}^+$							
1	0.052	0.0013	1.11×10^{-2}	5.55	3.41	50.00	5.00
2	0.049	0.0038	3.05×10^{-3}	1.53	2.84	13.75	3.91
3	0.041	0.0060	1.29×10^{-3}	0.65	2.52	5.83	3.43
4	0.038	0.0079	1.24×10^{-3}	0.62	2.50	5.59	3.41
5	0.057	0.0102	7.93×10^{-4}	0.40	2.35	3.57	3.20
$^{99}\text{TcO}_4^-$							
1	0.055	0.0014	9.89×10^{-3}	2.47	3.03	50.00	5.00
2	0.035	0.0036	3.06×10^{-3}	0.77	2.58	15.49	3.98
3	0.035	0.0053	1.45×10^{-3}	0.36	2.31	7.35	3.55
4	0.030	0.0069	3.34×10^{-3}	0.84	2.61	16.91	4.04
5	0.438	0.0184	4.27×10^{-5}	0.01	1.91	0.22	2.15
6	0.020	0.0296	1.59×10^{-3}	0.40	2.35	8.02	3.60
7	0.063	0.0316	2.55×10^{-4}	0.06	1.91	1.29	2.77
8	0.068	0.0349	6.83×10^{-5}	0.02	—	0.35	2.30
9	0.050	0.0377	3.69×10^{-4}	0.09	—	1.87	2.92
10	0.044	0.0401	1.21×10^{-4}	0.03	—	0.61	2.49
11	0.064	0.0427	6.09×10^{-5}	0.02	—	0.31	2.53
12	0.043	0.0453	1.28×10^{-4}	0.03	—	0.65	2.52
13	0.065	0.0480	1.26×10^{-4}	0.03	—	0.64	2.51
14	0.048	0.0508	5.93×10^{-5}	0.01	—	0.30	2.25
NO_3^-							
			(Conc., g/g)				
1	0.052	0.0013	5.34×10^{-3}	1.08	2.70	50.00	5.00
2	0.049	0.0038	1.81×10^{-3}	0.36	2.31	16.93	4.04
3	0.041	0.0060	7.84×10^{-4}	0.16	2.04	7.34	3.55
4	0.038	0.0079	1.04×10^{-3}	0.21	2.13	9.76	3.70
5	0.057	0.0102	4.69×10^{-4}	0.09	1.91	4.39	3.29
6	0.023	0.0122	1.64×10^{-4}	0.03	—	1.54	2.84
7	0.032	0.0135	2.06×10^{-4}	0.04	—	1.93	2.93
8	0.084	0.0163	7.48×10^{-5}	0.02	—	0.70	2.54
9	0.048	0.0196	5.39×10^{-5}	0.01	—	0.50	2.42
10	0.053	0.0221	3.75×10^{-5}	0.01	—	0.35	2.30

Appendix L

Measurement of Water Vapor Diffusion Through Asphalt Diffusion Barrier Material

Appendix L - Hanford Grout Performance Assessment
Measurement of Water Vapor Diffusion Through
Asphalt Diffusion Barrier Material

G. A. Whyatt
L. K. Fetrow

February 1992

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

Summary

A solid asphalt/aggregate diffusion barrier currently surrounds the grout disposal vaults. One potential mechanism for long-term release from the grout vaults involves the diffusion of water vapor through the diffusion barrier to the grout. The diffusing water vapor then condenses and drips to the soil carrying contamination with it. The diffusion of the water vapor is driven by a depression in the vapor pressure over the grout caused by the high salt content in the grout waste form.

This report describes the results of experiments intended to quantify the rate at which water vapor diffuses through the solid asphalt/aggregate diffusion barrier. Tests were conducted using lab-prepared samples over a range of air void contents and at two asphalt contents. The asphalt contents were selected as 7.0 wt% and 6.5 wt% on a total mix basis. These correspond to the minimum asphalt content and 0.5 wt% less than the minimum allowed in the construction specification.

In addition, a core sample was taken from the diffusion barrier of vault 105 during construction. Two samples were prepared from this core and were tested in the diffusion apparatus to confirm results obtained on samples prepared in the laboratory.

A reasonable value of diffusivity for the minimum asphalt content (7.0 wt%) and maximum air void content (4.0%) allowed in the construction specification is $2 \times 10^{-5} \text{ cm}^2/\text{s}$. Higher asphalt contents and lower void contents result in lower diffusivities. Samples prepared with 6.5 wt% asphalt had diffusivities approximately twice as high at 4% void content. However, diffusivities of $2 \times 10^{-5} \text{ cm}^2/\text{s}$ are still attainable if the material is compacted to a sufficiently low void content.

The diffusivity value of $2 \times 10^{-5} \text{ cm}^2/\text{s}$ can be applied in performance assessment calculations to estimate the impact from water vapor diffusing through the intact diffusion barrier. A simple, conservative analysis for drinking-water exposure from a low-volume well indicates that the impact will be approximately 1% of the 4 mrem/yr limit. However, the current PA will consider the impacts of cracking and long-term degradation of the diffusion barrier. Seismic events and biodegradation of the asphalt may eventually open cracks in the diffusion barrier. The amount of water vapor diffusing through these cracks may exceed the amount diffusing through the solid barrier material.

Introduction

Disposal of the low-level fraction of liquid radioactive wastes stored in double-shell tanks on the Hanford Site is scheduled to begin in the 1990s. Disposal will consist of mixing the liquid wastes with cementitious grout-forming solids. The resulting slurry will be pumped into reinforced, 5300 m³ concrete vaults, where it will harden into a cementitious mass. A diffusion barrier completely surrounds each vault to limit the release of contaminants from the vault to an acceptable level. The current performance assessment two-dimensional modeling effort is focused on modeling two release mechanisms: 1) release by diffusion of contaminants through the grout, concrete vault, and diffusion barrier and 2) advection of water through the grout, resulting from cracks in the diffusion barrier and concrete vault.

The data presented in this report is useful in evaluating a third mechanism termed "water vapor return." The grout contains high concentrations of salts that depress the equilibrium vapor pressure of the pore water within the grout. The soil porosity is at approximately 100% relative humidity since it is in equilibrium with moisture contained in the soil. This provides a driving force for diffusion of water vapor from the soil to the grout. The diffusing water eventually saturates the grout and produces a drip. Since the performance assessment looks at the radiological impacts of disposal over extended time periods, the liquid is assumed to leak from the catch basin through some small flaw in the barrier.

To evaluate the possibility of release through the water vapor diffusion mechanism, laboratory tests have been performed to directly measure the rate of water vapor diffusion through a low-void asphalt pavement barrier material. Results are reported for lab-prepared samples with the minimum asphalt content and with less than the minimum asphalt content at a variety of void contents. The values obtained are then interpreted in terms of the current groundwater and drinking water scenario assumptions. Test results from samples of a core taken during the construction of vault 105 are also presented.

Experimental Design

The experimental apparatus (Figure L.1) consisted of a Cahn model 2000 electrobalance, sealed in a glass housing. For testing lab-prepared samples, the balance was connected through a 2.54-cm (1-in.) diameter, 45.7-cm (18-in.) long flex hose to a diffusion cell consisting of a 10.2-cm (4-in.) diameter pipe with barrier material compacted in it. For testing of core samples, the flex hose length was reduced to 12.7 cm (5 in.) and the core sample was cut to length and sealed into a 15.2-cm (6-in.) diameter pipe.

Figure L.1. Schematic of Experimental Configuration

One side of the sample was maintained at 100% relative humidity. The other side of the sample was connected to the flex hose leading to the electrobalance. A nylon bag of desiccant (anhydrous magnesium perchlorate) was suspended from the electrobalance. The weight gain of the desiccant over time was recorded on a strip chart recorder. Measurements were made throughout several weeks to ensure that the rate was at steady-state.

The nominally 15-cm (6-in.) diameter core samples of the diffusion barrier were cut with a diamond saw to a length of 8.3 cm (3.25 in.). The cut for the "wet" side of the sample was performed with water as a lubricant. The "dry" side was cut without lubricant to avoid trapping water in the surface of the sample. The outside diameter of the sample was 14.3 cm (5.625 in.). The core was placed in a sample holder with a 0.38-cm (0.15-in.) gap around the outside of the sample. This gap was filled with AR-6000 asphalt to provide a seal around the edge of the sample. Rubber gaskets with an I.D. of 12.7 cm (5.0 in.) were placed on the top and bottom of the sample to prevent asphalt from leaking or covering the surface of the sample. The bottom of the sample was supported by a stainless steel wire grid, which in turn was supported by a perforated plate. This prevented the sample from sagging or cracking during the test.

The electrobalance was required in order to measure the low rates of water vapor diffusion through the sample. Because the rates were very low, the inleakage to the scale through O-ring seals in the balance enclosure reduced the sensitivity of the device for detecting water vapor diffusion through a sample. To reduce the rates of inleakage, AR-6000 asphalt was used to seal O-ring joints. Ground glass joints were also sealed with asphalt at the top of the joint.

In some cases, the entire apparatus was placed inside a glove box in which humidity was maintained at a reduced level to improve the sensitivity of the measurements. The humidity within the glove box was lower than room air but higher than inside the dry side of the experimental apparatus. The lower humidity in the experimental apparatus was confirmed by disconnecting the diffusion cell and noting the increase in the rate of weight gain when the end of the flexible metal hose was exposed to the air within the glove box. Even with the reduced humidity of the glove box, some inleakage of moisture to the system occurred.

For all lab-prepared samples, a baseline was obtained with a plug in the end of the flexhose instead of a sample. This baseline was then subtracted from the measurement with a sample attached to obtain the amount of weight gain due to diffusion of water vapor through the sample. The baseline was remeasured for each sample. For core samples, the baseline was obtained by measuring the rate with the sample chamber attached prior to adding water to the lower chamber.

The compaction of the lab-prepared samples was performed in the lab using a device equivalent to a Marshall hammer (ASTM D 1559). The repeated blows delivered by a 4.536-Kg (10-lb) weight dropped from a height of 45.7 cm (18 in.) provided compaction of the samples. In ASTM D 1559, the sample is compacted from both sides. In this work the sample was compacted from one side only so that

a seal could be maintained between the sample and the compaction mold. The number of blows determines the degree of compaction of the sample. The more compaction, the lower the air void content and the lower the water vapor diffusivity.

Laboratory samples were prepared using the mix design prepared for construction of the diffusion barrier to surround the grout vaults. The asphalt was AR-6000 obtained from U.S. Oil in Tacoma. The construction specification requires 7.5 ± 0.5 wt% asphalt. The amount of asphalt used in initial tests was 7.0 wt% of the total mix. Therefore, these samples contain the minimum allowable asphalt content. Additional samples were prepared with an asphalt content of 6.5 wt% of total mix. These samples represent material that is too lean in asphalt in order to evaluate the severity of the impact of missing the specification.

The aggregate was obtained from ACME Concrete in Richland and was screened to meet the specification shown in Table L.1. The aggregate was marinated with the lime mixed with water prior to heating and coating with the asphalt. This step is performed on the barrier aggregate to prevent stripping by improving the asphalt-aggregate bond.

The marinated gravel was dried and heated in an oven to 135°C . The asphalt was then heated (but not above 135°C) to allow it to pour easily and the asphalt and aggregate were mixed. After mixing, the mixture was placed back in the oven to bring the temperature back to 135°C . The compaction mold was preheated in the oven with the asphalt mix to 135°C . The Marshall hammer was warmed on a hot plate prior to use to avoid cooling of the asphalt mix during compaction. The thickness of samples varied from 2.5 cm to 7.6 cm (1 to 3 in.).

Low-void samples sealed against the side of the compaction mold. However, some higher void samples did not seal against the side of the mold so that the primary diffusion path was along the interface between the cell wall and the sample rather than through the sample. This led to a high reading even if the sample itself was fairly impermeable to water vapor. To determine if the sample was sealed against the cell wall, one end of the sample was covered with water, and a small helium pressure was applied to the other end of the sample to check for bubbles. If the sample was not sealed against the cell, it was removed from the cell, weighed, and extra asphalt was used to seal the edge of the sample against the cell wall. The sealing process produced a 0.64-cm (0.25-in.) bead of asphalt around the edge of the sample. The area covered by this bead was subtracted from the sample area in calculating the diffusivity for the sample. The weight of asphalt added was taken into account in calculating the density for determination of void content.

The density of pavement samples was measured using ASTM D1188/D 2041. In this procedure the sample is weighed and then cooled and coated with paraffin. The sample is then weighed again in air and then weighed immersed in water. The purpose of the paraffin is to seal the surface of the sample to prevent intrusion of water into the sample during immersion. Using this procedure, the standard

Table L.1. Aggregate Sizing for Laboratory Samples

Specification Screen Size (in.)	Wt% Passing in Specification ^(a)	Screen Size Used (in.)	Wt% Passing Used in Sample Preparation
5/8 in.	100	5/8 in.	100
1/2 in.	92 - 100	1/2 in. ^(b)	100
3/8 in.	85 - 95	3/8 in.	90
No. 4	65 - 75	No. 4	70
No. 16	36 - 42	No. 18 ^(c)	39
No. 30	27 - 33	No. 30	30
No. 50	16 - 22	No. 45 ^(c)	19
No. 200 ^(d)	3.5 - 7.5	No. 200 ^(d)	5.5
lime pass No. 200	2.75 - 3.25	lime pass No. 200	3.0

- (a) From B-714-C2 specification Rev. 1, section 02147. Values include the weight of lime except as noted for the No. 200 sieve.
- (b) Due to the relatively small thickness of the samples being prepared, the 100 passing end of the specification was selected. This prevents a single aggregate particle from spanning half of the sample thickness.
- (c) The screen size was selected because it was the closest size that was immediately available. The minor difference is not expected to have any significant impact.
- (d) Wt% of aggregate passing. Does not include the lime, which is shown separately below.

deviation is 0.32% void content (determined by ASTM). The procedure used is more accurate and precise than ASTM D 2726/D 2041 that is commonly used for road pavements in which a "saturated surface dry" weight is used to correct for water intrusion during immersion.

Experimental Results

The calculation of diffusivity was performed assuming a one-dimensional steady-state process. The equation for one-dimensional diffusion can be rearranged to solve for diffusivity as a function of measured properties as shown below.

$$D = (m \, dX)/(A \, dC) \quad (1)$$

where D = diffusivity
 m = mass rate of water diffusion
 dX = thickness of sample
 A = area of sample
 dC = difference in concentration across sample

Lab Samples, 7.0 wt% Asphalt - The results of experimental water vapor diffusivity measurements using 7.0 wt% asphalt are shown in Table L.2. The footnotes to the table explain the details of each measurement. Some early points are noted as low confidence. The low confidence stems from a possible scale calibration error as well as an increase in confidence in later samples. This is due to the improvement in procedures and equipment used in determining the void content as well as the relatively low level of the baseline for the vapor diffusion measurement. The highest confidence data are plotted in Figure L.2. It is believed that the variability in the data may be greater than suggested by the small scatter about the line. The void content measurements are believed to be within about 0.5% void of the true value.

Lab-Prepared, 6.5 wt% Asphalt - After results in Table L.2 were obtained, additional tests were performed to determine the water vapor diffusivity of samples prepared with asphalt content below the construction specification range. Samples were prepared and tested at 6.5 wt% asphalt (total mix basis). The data are shown below in Table L.3. Figure L.3 shows the data from Tables L.2 and L.3 plotted together. The lower asphalt content appears to increase the diffusion rate of water vapor through the samples. Low diffusion coefficients can still be obtained in the 6.5 wt% asphalt material at low void contents.

Core Samples - Two samples from a core of actual barrier material were tested to confirm results obtained with lab-prepared material. The core was taken from vault 105, east of the leachate sump area with an elevation of 186.8 m (613 ft) at the top of the core. The compaction in this area was performed using a small vibratory steel roller and a small vibratory plate compactor.

Table L.2. Summary of Measurements on 7 wt% Asphalt Samples^(a)

Sample	% Air Voids ^(b)	Thickness (cm)	Wt Gain (mg/d)	Baseline (mg/d)	D_e (cm ² /s)
scoping	1.5 ^(c,d)	2.54	1.6	(e)	$<2.5 \times 10^{-5}$
1	$>3.6^{(d,f)}$	2.79	5.4	2.3	5.2×10^{-5}
2	$>5.8^{(d,f)}$	3.18	7.3	3.0	8.4×10^{-5}
3	0 ^(c,d)	2.47	0.6	0.41	5.0×10^{-6}
4	2.1 ^(c)	2.79	0.62 ^(g)	0.55	$<3.4 \times 10^{-6}$
6	2.4 ^(c)	3.02	0.69 ^(g)	0.59	$<3.7 \times 10^{-6}$
16 ^(h)	5.0 ^(c)	7.14	1.22	0.73	2.1×10^{-5}
24	3.8 ^(c)	5.49	1.32	0.80	1.8×10^{-5}
25	6.1 ^(c)	4.45	1.23	0.63	$3.4 \times 10^{-5(i)}$

- (a) 7.0 wt% on total mix basis.
- (b) Construction specification is 4% maximum voids.
- (c) Determined using ASTM D 1188/D 2041. Single operator precision $\sigma=0.32$, acceptable range of two results on identical samples 0.91.
- (d) Value may be affected by scale malfunction.
- (e) No baseline obtained, weight gain includes inleakage rate.
- (f) Determined using ASTM D 2726/D 2041. Saturated surface dry weight was not recorded, making the reported voids lower than actual. These samples are believed to have greater than four voids. If correctly executed, D 2726/D 2041 has a single operator precision $\sigma=.51$, acceptable range=1.44. Multilaboratory precision $\sigma=1.09$, acceptable range of results 3.08.
- (g) The smallest difference that can be reliably detected between baseline and weight gain with the cell attached is approximately 0.2 mg/d. These samples had rates less than 0.2 mg/d above baseline, so 0.2 mg/d was used to calculate the diffusivity.
- (h) This sample used mix obtained from the construction site rather than mix prepared in the laboratory. Compaction was performed in the Laboratory. The asphalt content may be greater than 7.0 wt%.
- (i) A significant amount of asphalt was added to the perimeter of the top and bottom edges to seal the sample in the cell. The diffusivity was adjusted upward to account for the reduction in surface area of exposed sample.

The results verify measurements of lab samples that indicated very low diffusion rates of water vapor through the barrier material. Water vapor diffusion rates were not high enough to produce a

Figure L.2. Plot of Diffusivity as a Function of Void Content. Data points plotted include samples #4, 6, 16, 24, 25. The sample at 5.0 wt% voids was prepared in the laboratory using mix obtained from the construction site. The asphalt content may be greater than 7.0 wt% for this sample.

noticeable change in the baseline water collection rate. However, even without baseline correction, the diffusion rates are low. Although the sensitivity was reduced for the core sample measurements, it is estimated that the diffusivity is less than $2 \times 10^{-5} \text{ cm}^2/\text{s}$, which is the expected diffusivity for a 7.0 wt% asphalt, 4% void, lab-prepared sample. This is believed to be due to a higher asphalt content^(a) and a lower void content.

The reduced sensitivity experienced during core sample tests was the result of a higher baseline rate than in the smaller 10.2-cm (4-in.) diameter lab-prepared samples. It is possible that some water was trapped inside the sample during core drilling and contributed to the higher rate. In any case, the rate dropped very slowly over a long period of time. In testing the cores, the water was not added to the lower

(a) The asphalt content of the core sample was not measured. However, lab samples were prepared at the minimum asphalt content of the construction specification so it is expected that the field-placed material contained more asphalt than lab samples.

Table L.3. Summary of Measurements on 6.5 wt%-Asphalt Samples^(a)

Sample	Void Content (%)	Thickness (cm)	Wt. Gain (mg/d)	Baseline (mg/d)	D_e (cm ² /s)
91-9	3.0	2.15	1.07	0.05	3.4×10^{-5}
91-10	6.6	2.24	4.58	-0.0	2.1×10^{-4}
91-12 ^(b)	-	-	-	-	-
91-13	1.7	2.19	0.325	-0.0	1.1×10^{-5}
91-14	3.4	5.25	1.04	0.10	3.0×10^{-5}

- (a) 6.5 wt% on total mix basis. Samples 91-1 through 91-8 (not shown) were produced to obtain a compaction curve and do not provide vapor diffusion data.
- (b) Sample 91-12 was compacted to 60 blows, which should correspond to a void content of approximately 5%. This sample had open pathways for air movement and was not tested further.

Figure L.3. Comparison of Water Vapor Diffusivity as a Function of Void Content at 6.5 wt% and 7.0 wt% Asphalt (total mix basis). The high 6.5 wt%, 6.6% void sample had a minor leak in the sample itself. The line was plotted excluding this point.

chamber until a reasonable baseline was obtained. After addition of a water source in the lower chamber, the rate of moisture collection continued to fall. There was no apparent response to the rate of water collection at the electrobalance to the presence of the moisture in the source cup. Therefore, if calculated in the normal way these samples would result in a zero diffusivity. To provide some quantification of the results, a range of diffusivity is provided in Table L.4 along with the sample thickness, void content, and baseline prior to water addition to the lower chamber.

This range provides the diffusivity of 0 (zero) resulting from subtraction of the baseline, and a diffusivity value determined by neglecting the baseline and assuming the entire weight gain is due to diffusion through the sample. The upper value provides a conservative bound on the diffusivity for these samples.

The rate of weight gain for each of the two core samples is provided in Figures L.4 and L.5. As can be seen in the figures there is no clear response from the system when moisture is added to the lower chamber. In addition, there was no response from the second core sample test when the water was removed and replaced with desiccant at the end of the test. It takes a very long time to reach a low rate of weight gain in the tests. While testing the first core sample, core sample #2 was stored in a desiccated environment. The fact that the data is better behaved and reaches a lower value for the second sample may indicate the presence of some water within the core resulting from core drilling operations. If this is the case, the water collection rate is controlled by water vapor diffusing out of the sample rather than through the sample from the lower chamber.

Table L.4. Summary of Vault 105 Core Sample Measurements

Sample	Sample Thickness (cm)	Void Content (%)	Rate of wt Gain (mg/d)	Baseline Rate of wt Gain (mg/d)	Diffusivity Range (cm ² /s) ^(a)
core 1	8.3	0.5	0.91	1.14	0 - 3.8 x 10 ⁻⁵
core 2	8.3	0.3	0.49	1.13 ^(b)	0 - 2.0 x 10 ⁻⁵

- (a) In both cases the initial baseline with no water present in the source cup produced results lower than the rate obtained after water addition. The upper limit value is calculated with no correction for the baseline rate of weight gain.
- (b) At the end of the test, the water in the source cup was replaced with desiccant. The final baseline was measured at 0.46 mg/d.

Figure L.4. Rate of Weight Gain of Desiccant for Core #1 vs. Days Connected to the Electrobalance. The lower graph shows an expanded scale to provide more detail in the nearly level region. Water was added to the lower chamber after 57 days.

Figure L.5. Rate of Weight Gain of Desiccant for Core #2 vs Days Connected to the Electrobalance. The lower graph shows an expanded scale to provide more detail in the nearly level region. Water was added to the lower chamber after 35 days. At 139 days, the water in the lower chamber was removed and replaced with desiccant.

Interpretation of Results for Performance Assessment

Lab-prepared samples indicate that at the minimum asphalt content (7.0 wt%) and the maximum void content (4.0%) a diffusivity value less than $2 \times 10^{-5} \text{ cm}^2/\text{s}$ can be expected. The baseline for core sample #1 corresponds to a diffusivity of $3.8 \times 10^{-5} \text{ cm}^2/\text{s}$. A 50% change in the baseline would have been detectable in this test. Therefore, the diffusivity for core sample #1 is believed to be less than $2 \times 10^{-5} \text{ cm}^2/\text{s}$. Core sample #2 indicated a baseline of $2 \times 10^{-5} \text{ cm}^2/\text{s}$ with no response to water placement in (or removal from) the source cup. Therefore, a diffusivity of $2 \times 10^{-5} \text{ cm}^2/\text{s}$ has been selected as a reasonably conservative value for the water vapor diffusivity of intact barrier material.

A required diffusivity of the diffusion barrier was calculated using the following assumptions:

- Consider only ^{99}Tc and ^{129}I dispersed evenly into cold grout and concrete. Grout $R_f = 1.0$ for ^{129}I and $R_f = 5.0$ for ^{99}Tc
- isothermal system at 17°C with 83% relative humidity over grout (after dilution of salts to concrete and cold grout porosity value is 88% relative humidity) and 100% relative humidity outside barrier
- Water vapor diffusion rate is assumed to reach pore volume concentration and is then placed into site recharge to evaluate well concentration. (Ignore transport in vadose and saturated zone other than dilution factor in well.)
- low-volume well dilution factor 0.01 applied to concentration of recharge to the aquifer for uniform 0.1 cm/yr recharge.
- 33 vaults with intact diffusion barrier 91.4-cm (3-ft) thick and area for diffusion of $3 \times 10^7 \text{ cm}^2$
- DOE Order 5400.5 dose conversion factors used to calculate drinking water doses.

Based on these assumptions, a water vapor diffusivity of $2.0 \times 10^{-3} \text{ cm}^2/\text{s}$ would provide a release approximately equal to the 4 mrem/yr drinking water limit. This maximum allowable value is two orders of magnitude higher than measured values.

Application of a $2 \times 10^{-5} \text{ cm}^2/\text{s}$ diffusivity in the simple model described above results in a dose of 4.0×10^{-2} mrem/yr or about 1% of the limit. Therefore, the diffusion of water vapor through an intact diffusion barrier is not expected to be of concern. The calculated impact is directly proportional to the diffusivity value.

The major contributors to the difference in impact estimated here and in the January 1991 draft PA are changes in the assumptions for the well intercept and resulting dilution, ^{99}Tc sorption, inventory, and apportionment.

Water vapor diffusion through cracks still has the potential to be a major contributor to release. A conservative calculation indicates a 91.4-cm (3-ft) thick barrier with a 5.0-cm crack running the circumference of the vault could contribute up to 21% of the low-volume well drinking water limit. The result is directly proportional to crack area so this could represent a number of smaller through-wall cracks. This value was calculated using the following assumptions:

- Only ^{99}Tc and ^{129}I considered in dose calculation.
- Grout $R_f=1.0$ for ^{129}I and $R_f=5.0$ for ^{99}Tc .
- Cracks are completely open and straight.
- Contamination is uniform in grout, cold grout, and concrete porosity.
- Transport of water to outside of crack and transport of contaminant to inside of crack are rapid so that release is controlled by diffusion in the air phase.
- Pseudo-steady state value, no time associated with the dose.
- No interaction with other release mechanisms considered.
- Dose calculated using DOE Order 5400.5 dose conversion factors.

This calculation will be refined in the performance assessment to account for the diffusive resistance of the grout, the effects of the vadose zone, and other factors.

Appendix M

Exposure Scenarios and Sources for Parameters

Appendix M

Scenario Descriptions

K. Rhoads and S. F. Snyder, Pacific Northwest Laboratory

Following the disposal of grouted waste, individuals or populations may be exposed to radioactive or hazardous materials contained in the grout via a number of pathways. Mechanisms for release of these materials from the Grout Disposal Facility include intrusion into the burial site, direct soil contamination by upward diffusion of radionuclides from the grout, disruption of the disposal facility by natural events, leaching of materials to groundwater, and subsequent transport of groundwater to the Columbia River. The intruder, upward diffusion, and groundwater pathways would be expected to affect a relatively small number of individuals, whereas exposure via the river may impact a much larger population. Eight scenarios for human exposure to radioactive materials from the Grout Disposal Facility were evaluated for this performance assessment. Individual doses were evaluated for two intruder scenarios—one for an individual who drills a well through the disposal facility and another for a resident who inhabits the site after drilling is complete. Three individual scenarios involving use of contaminated groundwater were also considered for drinking water only, irrigation of a home garden, or irrigation of a family farm. The dose to an individual was calculated for two special cases involving upward diffusion from the buried grout in the absence of recharge from precipitation, and for disruption of the disposal site by a catastrophic flood. Collective dose was estimated for a large population using contaminated water from the Columbia River, and for a smaller population using groundwater from a community well. A summary of the exposure routes considered in each scenario is shown in Exhibit M.1.

Each scenario is described in detail in the following sections, and assumptions and parameter values specific to each scenario are provided. The intent of these dose calculations was to model a typical individual, therefore the parameters were selected to generate a "best estimate" dose, rather than a maximum dose. Because only a very small number of individuals exhibit behavior that maximizes their exposure to a particular pathway, the assumption of maximum exposure to all pathways simultaneously results in a situation that is frequently unrealistic (for example, consumption of all food types at the maximum rate implies a total food consumption substantially higher than an individual's annual intake). Therefore, an estimate of the more likely "typical" dose was generated by selecting parameter values indicative of average behavior. When published data were available to justify a typical parameter value, that value was used. However, a number of parameters are required for which there is no published, typical value (i.e., hours spent outdoors), in which case a reasonable but conservative estimate was chosen.

Exhibit M.1. Summary of Exposure Scenarios

	<u>Driller</u>	<u>Post-Driller</u>	<u>Drinking Water</u>	<u>Flood, Upward Diffusion, Irrigated Farm and Garden</u>	<u>River</u>
External exposure from:					
surface soils while:					
outdoors	X	X		X	X
indoors		X		X	X
buried materials while:					
outdoors	X	X			
indoors		X			
surface water					X
immersion in surface water					X
Inhalation of:					
resuspended soil while:					
outdoors	X	X		X	X
indoors		X		X	
Ingestion of:					
soil while outdoors	X	X		X	X
drinking water from:					
groundwater			X	X ^(a)	
surface water					X
contaminated food types:					
leafy vgs. other vgs. fruit		X		X	X
animal products				X ^(b)	X
aquatic foods					X
crops irrigated with:					
contaminated groundwater				X	
contaminated surface water					X
animal products fed with crops irrigated with:					
contaminated groundwater				X	
contaminated surface water					X

(a) This pathway was not considered in the flood and upward diffusion scenarios.

(b) These pathways were considered for the irrigated farm scenario, but not for the irrigated garden scenario.

M.1 Drilling Scenario

The drilling scenario considered a situation in which an individual would drill through the grout, exhume a portion of the buried material, and subsequently leave the site. This scenario results in the shortest exposure time of the scenarios evaluated, and the activities are assumed to be completed in approximately 1 week. Monuments, barriers, and markers may reduce the probability that such an intrusion could occur, but such measures would not entirely preclude it.

Drilling, either for water or mineral exploration, would transport buried grout to the ground surface. The driller was assumed to remove a cylindrical volume of grout and bring it to the surface in a powder or slurry form, depending on the drilling method used. All drilling debris was then assumed to be uniformly incorporated into the upper soil horizon. Pathways for radiation dose to the driller include external exposure, inhalation of resuspended material, and inadvertent ingestion of contaminated soil.

M.1.1 Scenario Description

The driller was assumed to drill a 30-cm bore through the entire 9.1-m depth of the grout, removing a total grout volume of 0.64 m^3 . As the driller removes material through the borehole to the surface, it would be distributed about the circumference of the borehole and subsequently covered over with more recently exhumed materials.

External exposure doses were assumed to occur over a period of 1 week, during which the driller would be exposed to external radiation from the exhumed grout for 40 hours. This takes into consideration the time required to complete well drilling, breakdown of the drilling equipment, and site grading. The drilling debris was assumed to be uniformly dispersed and graded over a 10- x 10-m area in the vicinity of the well to a depth of 15 cm.

Resuspension of the freshly bored grout by wind or mechanical disturbance introduces a mechanism for inhalation exposure. The driller was assumed to be exposed to the resuspended material for one hour, after which the grout tailings would be covered with more recently exhumed, uncontaminated soil.

Inadvertent ingestion of the exhumed grout tailings was also assumed to occur. The mechanisms for this pathway include ingestion of resuspended dust and soiled-hand-to-mouth contact during the workday.

M.1.2 Scenario Parameters

Pathways considered in the drilling scenario dose calculations include inhalation, external exposure, and ingestion. The scenario-specific parameters used to calculate these doses are tabulated in Exhibit M.2.

Exhibit M.2. Parameter Specific to the Drilling Scenario

Drilling Scenario Parameter (units)	Best Estimate	Basis
Manual redistribution: deep soil/surface soil dilution factor (m)	6.4E-3	Calculated. Exhumed tailings uniformly distributed over a 100 m ² area.
Area over which drilling tailings were spread (m ²)	100	Scenario assumption
Hours of exposure to resuspended tailings (h)	1	Scenario assumption
Hours of exposure to ground contamination (h) (external dose)	40	Scenario assumption
Mass loading (g/m ³)	1E-4	U.S. EPA (1992). Data for Kennewick, Washington
Soil ingestion rate (mg/d)	100	U.S. EPA (1989)

M.2 Post-Drilling Home Garden Scenario

The post-drilling home garden scenario was used to estimate the dose for a resident on land that contains soil contaminated by grout tailings which were transported to the surface as a result of drilling through the burial site. Such a situation would occur subsequent to the drilling scenario, where grout tailings brought to the surface during well drilling could be graded into the local soil. This material would present a source of potential radiation exposure to people living on or near the site of original disturbance long after the initial contaminating event. A resident at the site was assumed to be exposed via external exposure, inhalation of resuspended soil, ingestion of crops grown in soil containing the excavated radioactive materials, and incidental soil ingestion. The resident's water supply was assumed to be free from contamination.

M.2.1 Scenario Description

A resident was assumed to occupy a home on the land in which the upper soil layer is uniformly contaminated with grout tailings. The volume of tailings distributed through the upper soil layer is equivalent to that removed in the drilling scenario, or 0.64 m³. The land area about which the contamination is spread was assumed to be 2500 m². A larger area was considered for this scenario than in the driller scenario because of additional spreading of contaminated soil during home construction. The outdoor soil, essentially the area of the garden, was assumed to be uniformly contaminated to a depth of 15 cm over the 2500 m² area. The resident in this scenario is exposed via external exposure, inhalation, and ingestion pathways.

External doses in this scenario are a result of exposure to penetrating radiation from radionuclides in the contaminated soil and buried waste. No external exposure doses were calculated for resuspended materials. See section M.1.1 for additional general details regarding external exposure calculations.

Inhalation doses result from the intake of resuspended soil. These doses were calculated by assuming full-time exposure to contamination dispersed in the outdoor air. This 24 h/d exposure to the outdoor air concentration conservatively estimates the indoor-plus-outdoor inhalation dose, because the outdoor air contains a greater mass loading of contaminated soil than indoor air. Indoor soil contamination results from the translocation of outdoor soil to the home interior by foot traffic and blowing dust. The assumption that the indoor-air radionuclide concentration is equivalent to that of the outdoor air overestimates the dose contribution from indoor air.

Ingestion doses in the post-drilling scenario result from consumption of crops grown in contaminated soil as well as inadvertent soil ingestion. The irrigation water source used to support crop growth was assumed to be free of contamination. A crop holdup time was not considered because the long half-life of the radionuclides involved results in negligible radiological decay for any reasonable holdup time between harvest and consumption. Inadvertent soil ingestion results from ingestion of blowing dust, ingestion of soil remaining on food crops, and hand-to-mouth contact.

The major food types assumed to come from the home garden include leafy vegetables (i.e., lettuce, spinach, cabbage), other vegetables (e.g., root crops, tomatoes, broccoli, cucumbers), and fruit (i.e., orchard crops). Cereals (e.g., wheat, oats) are not considered in this home garden scenario because space limitations preclude growing this type of crop in the contaminated area. The fraction of the total diet supplied by the individual's garden was assumed to be 0.25 for leafy and other vegetables and 0.20 for fruit (U.S. EPA 1989).

M.2.2 Scenario Parameters

The post-drilling scenario dose calculations considered external exposure, inhalation, and ingestion of food crops and soil. The scenario-specific parameters used to calculate these doses are tabulated in Exhibit M.3.

M.3 Drinking Water Scenario

The drinking water scenario was limited to exposure via direct consumption of contaminated groundwater. An individual was assumed to obtain drinking water from an aquifer containing leachate from the grout vaults. The leachate was assumed to travel through the unsaturated zone to the aquifer. No water treatment or hold-up between pumping and consumption of the water was considered.

Exhibit M.3. Parameters Specific to the Post-drilling Scenario

Post-drilling Home Garden Scenario Parameters (units)	Best Estimate	Basis
Hours of exposure to ground contamination (h) (external dose)	4383	Scenario assumption
Hours of inhalation exposure per year (h)	8766	Scenario assumption
Mass loading factor (g/m ³)	1E-04	U.S. EPA (1992). Data for Kennewick, Washington
Soil ingestion rate (mg/d)	100	U.S. EPA (1989).
Fraction of roots in the upper soil	1	Scenario assumption
Manual redistribution: deep soil/surface soil dilution factor (m)	2.6E-4	Calculated. Exhumed tailings distributed over a 2500 m ² area.
Area contaminated by grout (m ²)	2500	Scenario assumption
Crop growing time (d)		Scenario assumptions
Leafy vegetables	90	
Other vegetables	90	
Fruit	90	
Above-ground biomass (kg _{wet} /y)		Napier et al. (1988)
Leafy vegetables	2.0	
Other vegetables	2.0	
Fruit	3.0	
Fraction of diet produced locally		U.S. EPA (1989)
Leafy and other vegetables	0.25	
Fruit	0.20	
Consumption rate (kg _{wet} /y)		Multiple of local diet fraction values and consumption rates from the western region reported in Yang and Nelson (1986)
Leafy vegetables	4.1	
Other vegetables	13.9	
Fruit	7	

This scenario was used to demonstrate that the performance objective for groundwater protection would not be exceeded by leachate from the Grout Disposal Facility for a water intake rate of 2 L/d (730 L/yr), consistent with proposed regulations (56 FR 33050, U.S. DOE 1990).

M.4 Irrigated Farm Scenario

The second of the scenarios that considered agricultural pathways is the irrigated farm scenario. In this scenario, contaminated groundwater would be used to irrigate crops, and as a drinking water source for people and livestock. The farmhouse was assumed to be located at a sufficient distance downgradient from the grout disposal site that external penetrating radiation directly from the buried vaults was not considered. Doses to an individual on the farm result from external exposure, inhalation, and ingestion of food crops, animal products, and contaminated groundwater.

Prior to its establishment as a federal reservation, farms existed on what is now the Hanford Site. Currently, the region surrounding Hanford supports extensive agricultural activity, including production of fruit, wheat, vegetable crops, and meat and milk livestock. Therefore, a scenario that considers this type of irrigated farming is credible after institutional control of the site ends.

M.4.1 Scenario Description

The 20,000-m² farm was assumed to be located 100 m hydraulically downgradient from the grout disposal site where groundwater would be contaminated by radioactive materials in leachate from the vaults. The groundwater would then be used as a source of domestic water, livestock drinking water, and irrigation water at a rate of 45 m³ per day. External doses to an individual on this farm result from exposure to surface soil contaminated by irrigation water.

Inhalation doses result from the intake of contaminated soil resuspended by wind or mechanical disturbance, such as plowing. An individual was assumed to inhale air containing radionuclide concentrations equivalent to those in outdoor air for 8766 h/yr to determine the inhalation dose. The assumption that radionuclide concentrations in indoor and outdoor air were identical provides a conservative inhalation dose estimate, because outdoor air activity concentrations will always be equal to or greater than that of indoor air (see section M.2.1, post-drilling home garden scenario).

Both the surface soil external exposure calculation and inhalation dose calculation required estimates of the soil radionuclide concentration. The level of soil activity is related to the rate and duration of irrigation water application, which varies with the type of crop. To avoid apportioning farmer occupancy times in the various types of fields, the surface soil activity concentrations used for external dose calculations were calculated separately, using a single irrigation rate and growing season length.

Total ingestion doses combined the doses from the ingestion of food crops, animal products, groundwater, and inadvertent soil ingestion. Inadvertent soil ingestion results from ingestion of blowing dust, ingestion of soil remaining on food crops, and hand-to-mouth contact. All water consumed originates from the groundwater source, and the consumption rate is a population average rather than the 2 L/d rate used for the drinking-water scenario. Only a portion of the terrestrial food crops, and animal products, were assumed to originate from the family farm (see Exhibit M.4). The balance of

the diet was assumed to be grown in an uncontaminated location. All grains consumed by the farmer and livestock were assumed to be grown elsewhere on uncontaminated land and irrigated with uncontaminated water.

Radionuclides in the food crops result from irrigating the crops with contaminated groundwater and growing crops in soil contaminated by the irrigation water. For all food categories, holdup time was not considered because the long half-life of the radionuclides involved results in negligible radiological decay for any reasonable holdup time between harvest and consumption.

Radionuclides in animal products are a result of livestock consuming contaminated feed and water. "Meat livestock" (i.e. beef cattle) and dairy cows were assumed to consume fresh forage from the same field. Meat livestock were assumed to consume uncontaminated grain as a stored feed, whereas milk cows consumed stored hay that had been irrigated with the contaminated groundwater. Poultry were assumed to consume feed that was grown on an uncontaminated site. The only radionuclide intake for poultry and eggs results from water consumption.

In this scenario, the quantity of irrigation water required to support production of terrestrial foods and animal products is sufficiently great that the volume of the contaminated plume from the disposal site must be diluted by uncontaminated water from the aquifer. The groundwater concentrations predicted by the transport model were therefore reduced to account for dilution of the contaminated plume (see section 3.4.5).

M.4.2 Scenario Parameters

The irrigated farm scenario dose calculations considered external exposure, inhalation, and ingestion pathways. The parameters used to calculate these doses for the irrigated farm scenario are tabulated in Exhibit M.4.

M.5 Irrigated Garden Scenario

This scenario is similar to the irrigated farm, except that it omits the animal food consumption pathways, permitting use of a lower irrigation rate than the farm scenario. In this case, dilution of the contaminated groundwater plume by uncontaminated water from the aquifer was not assumed because of the lower water volume required for irrigation (see section 3.4.5). All other pathways and parameters in this scenario were identical to those discussed in section M.4 and listed in Exhibit M.4. This scenario was considered because it was not possible to determine in advance of completion of the groundwater modeling whether the increased radionuclide concentrations in groundwater would offset the lower consumption rate of contaminated foods and result in a higher dose to the maximally exposed individual compared with the irrigated farm scenario.

Exhibit M.4 Parameters Specific to the Irrigated Farm Scenario

Irrigated Farm Scenario Parameter (units)	Best Estimate	Basis
Inhalation dose exposure time (h)	8766	Scenario assumption
Hours of exposure to ground contamination (h)	4383	Scenario assumption
Mass loading (g/m ³)	1E-4	U.S. EPA (1992). Data for Kennewick, Washington
Soil ingestion rate (mg/d)	100	U.S. EPA (1989)
Fraction of roots in the upper soil, upper 15 cm	1.0	Scenario assumption
Irrigation water application rate (in./y)	32.4	Scenario assumption
Duration of irrigation (mo/y)	6.5	Typical availability for the Kennewick Irrigation District, Kennewick, Washington. (April 1 through October 15).
Human water consumption rate (L/y)	655	Roseberry and Burmaster (1992)
Local diet fraction		U.S. EPA (1989)
Leafy and other vegetables	0.25	
Fruit	0.20	
Milk	0.46	
Meat, poultry, and eggs	0.44	
Crop growing time (d)		Scenario assumption
Leafy vegetables	90	
Other vegetables	90	
Fruit	90	
Stored feed - milk	90	
Fresh forage - meat, milk	45	
Above-ground biomass (kg _{wet} /m ²)		Napier et al (1988)
Leafy vegetables	2.0	
Other vegetables	2.0	
Fruit	3.0	
Stored feed - milk	1.0	
Fresh forage - meat	1.0	
- milk	1.5	

Exhibit M.4. (contd)

Irrigated Farm Scenario Parameter (units)	Best Estimate	Basis
Consumption rate (kg _{wet} /y)		Multiple of local diet fraction values and consumption rates from the western region reported in Yang and Nelson (1986).
Leafy vegetables	4.1	
Other vegetables	13.9	
Fruit	7.0	
Meat	22	
Poultry	4.6	
Milk	50.8	
Eggs	10.6	
Animal diet fraction		Scenario assumption
Stored feed - milk	0.25	
Fresh forage - meat,milk	0.75	
Livestock water intake rate (L/d)		Napier et al. (1988)
Meat livestock	50	
Dairy cows	60	
Poultry and laying hens	0.3	

M.6 Special Cases

Two special cases involving direct contamination of surface soil were evaluated in addition to the groundwater scenarios. These cases involved contamination of the upper soil surface either by upward diffusion of radionuclides from the grout vaults in the absence of recharge from precipitation, or by disruption of the disposal facility by a catastrophic flood. The upward diffusion scenario was similar to the intruder post-drilling garden scenario (see section M.2), except that both surface and deep soil layers were considered to be contaminated at similar levels. Otherwise, the same pathways and parameters were used for both cases. Soil concentrations for the upward diffusion scenario were estimated using the subsurface transport model for times up to 660,000 years after disposal.

Pathways considered in the flood scenario were similar to the farm scenario, except that irrigation water and drinking water were assumed to be uncontaminated (see Exhibit M.4). The soil concentrations in the flood scenario were based on dispersion of the entire grout inventory in three different volumes, corresponding to 1) the volume used for the 200 Area plateau (78 km² x 4 m deep) in the HDWEIS (U.S. DOE 1987), 2) the Hanford Site (1,450 km² x 10 m deep), or 3) the Pasco Basin (4,850 m² x 10 m deep). The flood scenario is evaluated at 50,000 years after disposal, because this is the approximate predicted time for recurrence of glacial flooding of sufficient severity to disturb the disposal site (see section 2.1.5).

M.7 Columbia River Scenario

The Columbia River scenario was used to estimate dose to the population in the downstream Columbia River region from exposure to contamination in the river. The contamination is the result of groundwater flow into the surface water system. The Columbia River is presently used for drinking water, irrigation, and recreation by a limited number of people living downstream of Hanford, and for the purposes of this analysis, these uses are assumed to increase in the future. Population doses in the river scenario result from external exposure, inhalation of resuspended soil, and ingestion pathways. Doses to individuals were not considered because they would be substantially lower than those in the groundwater scenarios. Radionuclide concentrations in river water are lower than in groundwater as a result of dilution by uncontaminated river water originating upstream from Hanford.

River contamination was assumed to result from contaminated-groundwater recharge to the Columbia River. The groundwater contamination occurs by transport of radioactive leachate from the disposal site through the vadose zone to the aquifer system. The rate at which radionuclides subsequently enter the river depends on the rate at which they enter the groundwater, the extent of radioactive decay, chemical characteristics, the flow rate of the aquifer, and distance to the river.

This scenario is similar to the irrigated farm scenario except that surface water, rather than groundwater, would be used for irrigation and human and animal consumption. Additional pathways were included to evaluate the dose from recreational uses of the Columbia River including swimming, boating, fishing, other shoreline activities, and consumption of fish caught in the river. Dose to the regional population was calculated in this scenario because of the potential for exposure of a larger number of people than in the groundwater scenarios.

At present, this scenario is very conservative for a number of reasons, and would be expected to provide an upper bound to potential exposure of downriver populations in the future. Irrigation water for the majority of the Columbia Basin is obtained from reservoirs located upstream of the Hanford Site, and which are uncontaminated by groundwater coming from beneath the site. Production of all food consumed by the downriver population with contaminated water would require a very large increase in crop production below the site, and a substantial investment in new irrigation projects in this area. The Columbia River is also diluted by a large inflow of water from tributaries immediately below the Tri-Cities area and along its entire course to the Pacific Ocean, resulting in significantly lower radionuclide concentrations than those assumed for this analysis. The availability of alternate sources of drinking and irrigation water from uncontaminated tributaries and groundwater aquifers would further reduce the potential exposure levels for this population.

M.7.1 Scenario Description

The population dose estimates for this scenario result from regional use of the Columbia River as a drinking water supply and irrigation water source. In addition, the river provides a source of recreation. A total of 5 million people were assumed to reside along the river from the Hanford Reach to

the mouth. This represents a significant population increase over present conditions and is a conservative scenario assumption. This same population was used for a previous prospective population dose estimate (U.S. DOE 1989).

External doses result from exposure to irrigated land and from recreational exposure to contamination in the river water. In this scenario, the application rate of Columbia River water used for irrigation is lower than that used in the other scenarios because of differences in climate for the region being considered. The population for this scenario is distributed along the river from the arid climate of the Hanford Reach to the wetter coastal areas. The "average" irrigation rate for this scenario was determined from the precipitation and irrigation rates in Benton County by assuming that the same total quantity of water from precipitation plus irrigation would be required to support crop production all along the river. Because of the higher evapotranspiration rate in the Benton County region, this method probably overestimates the actual irrigation rates required for crop production in the more humid coastal areas, but it does provide a reasonable (and somewhat conservative) approximation.

In this scenario, internal doses may result from inhalation of resuspended soil. An individual was assumed to be outdoors 8766 h/yr for inhalation dose calculations. The indoor air radionuclide concentration was assumed to be equivalent to the outdoor air concentration. This provides a conservative inhalation dose estimate, because outdoor air concentrations will always be greater than or equal to that of indoor air.

Ingestion of food products contaminated by irrigation with river water provides another route for internal radiation exposures. The downriver population was assumed to subsist on its own agricultural products, which include the generalized categories of leafy vegetables, other vegetables, fruits, and cereals. The Columbia River was assumed to provide drinking water for both people and livestock, and all food for human consumption and animal feed crops were assumed to be irrigated with Columbia River water. Livestock consume both fresh feed (pasture grass) and stored feed. Stored feed consists of dry alfalfa hay for milk cows, and cereal grains for beef cattle and chickens (meat and egg layers). Inadvertent soil ingestion was also considered in this scenario.

M.7.2 Scenario Parameters

Columbia River scenario dose calculations consider external exposure, inhalation, and ingestion pathways. The parameters used to calculate these doses for the Columbia River scenario are tabulated in Exhibit M.5.

M.8 Community Well Scenario

This scenario uses the dose calculated for the individual garden scenario (section M.5) to estimate the potential collective dose via a community well. Based on a contaminated plume volume of $25 \text{ m}^3/\text{d}$ at 100 m from the disposal site, and an individual per capita consumption rate of $0.31 \text{ m}^3/\text{d}$

Exhibit M.5. Dose and Exposure Parameters Specific to the Columbia River Scenario

River Scenario Parameter (units)	Best Estimate	Basis
Population size	5.0E+06	Scenario assumption
Inhalation dose exposure time (h)	8766	Scenario assumption
Hours of exposure to ground contamination (h)	4383	Scenario assumption
Hours of recreation time (h)		Scenario assumption
Swimming	10	
Boating	0	
Shoreline	17	
Soil ingestion rate (mg/d)	100	U.S. EPA (1989)
Irrigation water application rate	25.0	USDA (1974). Calculated as average of Benton County average irrigation-plus-precipitation rates minus annual precipitation for counties adjacent to the Columbia River.
Duration of irrigation for surface soil external exposure and inhalation doses (mo/y)	6.5	Typical availability for the Kennewick Irrigation District, Kennewick, Washington. (April 1 through October 15).
Water consumption rate (L/y)	655	Roseberry and Burmaster (1992)
Regional diet fraction		Scenario assumption
All food types	1.0	
Consumption rate (kg _{wet} /y)		Consumption rates from the western region reported in Yang and Nelson (1986).
Leafy vegetables	16.5	
Other vegetables	55.0	
Fruit	35.0	
Cereal	74.0	
Meat	50.0	
Poultry	10.5	
Milk	115.0	
Eggs	24.1	
Fish	0.003	
Crop growing time (d)		Scenario assumption
Leafy vegetables	90	
Other vegetables	90	
Fruit	90	
Cereal	90	
Stored feed - milk	90	
Fresh forage	45	

Exhibit M.5. (contd)

River Scenario Parameter (units)	Best Estimate	Basis
Above-ground biomass		Napier et al. (1988)
(kg _{wet} /m ²)	2.0	
Leafy vegetables	2.0	
Other vegetables	3.0	
Fruit	0.8	
Cereal	0.8	
Stored feed - meat	1.0	
- milk	1.0	
Fresh forage - meat	1.5	
- milk		
Animal diet fraction		Scenario assumption
Stored feed - meat,milk	0.25	
Fresh forage - meat,milk	0.75	
Livestock water intake rate (L/d)		Napier et al. (1988)
Meat livestock	50	
Dairy cows	60	
Poultry and laying hens	0.3	
Feed intake rate (kg _{wet} /d)		Napier et al. (1988)
Meat livestock	68	
Dairy cows	55	
Poultry and laying hens	0.12	

for domestic use and limited gardening, the maximum number of individuals that could be supported by a community well without additional dilution is approximately 80. The collective dose from this scenario is therefore estimated as 80 times the individual dose for the garden scenario.

M.9 References

56 FR 33050ff. 1991. U.S. Environmental Protection Agency, "National Primary Drinking Water Regulations: Radionuclides." Notice of Proposed Rulemaking, 40 CFR Parts 141 and 142. *Federal Register*.

Napier, B. A., R. A. Peloquin, D. L. Strenge, J. V. Ramsdell. 1988. *GENII - The Hanford Environmental Radiation Dosimetry Software System*. PNL-6584, Vols. 1, 2, and 3. Pacific Northwest Laboratory, Richland, Washington.

Roseberry, A. M., and D. E. Burmaster. 1992. "Lognormal Distributions for Water Intake by Children and Adults." *Risk Analysis*, 12(1): 99-104.

U.S. Department of Agriculture (USDA). 1974. *1974 Census of Agriculture, Washington State and County Data*. Volume I, Part 47, Washington, D.C.

U.S. Department of Energy (DOE). 1990. *Radioactive Waste Management*. Order RL 5820.2A, DOE Richland Field Office, Richland, Washington.

U.S. DOE. 1989. *Draft Environmental Impact Statement, Decommissioning of Eight Surplus Production Reactors at the Hanford Site, Richland, Washington*. DOE/EIS-0119D, DOE, Washington, D.C.

U.S. DOE. 1987. *Final Environmental Impact Statement: Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes*. DOE/EIS-0113, Vol. 1-5, U.S. Department of Energy, Washington, D.C.

U.S. Environmental Protection Agency (EPA). 1992. National Air Data Branch, Aerometric Information Retrieval System. Total Suspended Particulate information for Kennewick, Washington (1985-88).

U.S. EPA. 1989. *Exposure Factors Handbook*. EPA/600/8-89/043, Washington, D.C.

Yang, Y-Y, C. B. Nelson. 1986. "An Estimation of Daily Food Usage Factors for Assessing Radionuclide Intakes in the U.S. Population." *Health Physics*, 50:245-257.

Appendix N

Sensitivity Analysis for Dose and Exposure Assessment Parameters

Appendix N

Sensitivity Analysis for Dose and Exposure Assessment Parameters

S. F. Snyder and K. Rhoads, Pacific Northwest Laboratory

A sensitivity analysis was performed for the dose and exposure assessment parameters used in the intruder (drilling and post-drilling), irrigated farm, irrigated garden, and Columbia River scenarios that were evaluated using the GENII computer code. The sensitivity analysis results reflect both the degree of uncertainty in each parameter value and that parameter's importance in determining the overall dose estimate for a particular scenario. In general, variations in values of the more sensitive parameters will produce significant changes in the dose estimate, whereas variations in parameters of low sensitivity will not significantly alter the calculated dose estimate. The analysis is intended to show the relative contribution of variations in scenario parameters to uncertainties in the resulting dose estimate.

N.1 Sensitivity Analysis Methods

The GENII-S computer code, described in Appendix I, Section I.3, was used to perform the sensitivity analyses. The code uses the basic exposure and dosimetry algorithms in the GENII software package, with an added feature that allows the user to define probability distribution functions (PDF) for a number of variable parameters. Possible choices for PDFs in the GENII-S code include fixed, uniform, loguniform, normal, lognormal, triangular, and empirical. A fixed PDF is specified by a single value for a parameter; the uniform and loguniform PDFs require minimum and maximum values; upper and lower 99.9% confidence limits define a normal or lognormal distribution; and the triangular distribution requires the definition of a minimum, maximum, and central value. The empirical distribution function allows the user to supply a set of raw data for a given parameter. The PDF for a particular parameter reflects the degree of uncertainty concerning its true value, which may result either from inadequate knowledge, or inherent stochastic variability in the parameter's value, or both.

In performing the sensitivity analysis for each scenario, a specified number of dose calculations were performed using a randomly selected set of values for the variable parameters in each run. In this analysis, a Latin Hypercube sampling technique was used to select a set of parameter values for each of 100 iterations based on the previously defined distributions. When inadequate empirical data was available to define a PDF, a uniform distribution over a range was assumed. Although attempts were made to

define the PDFs for each parameter as realistically as possible, many ranges were defined by default as $\pm 50\%$ of the value used in the deterministic (single point) dose calculations.

Output from the sensitivity analysis consisted of a series of partial rank correlation coefficients (PRCC) between the variable input parameters and the resulting dose estimates for each set of calculations. The relative sensitivity of each parameter was indicated by the absolute value of its partial rank correlation coefficient. The value of the PRCC may range from -1 to 1, where a PRCC of 1 indicates a perfect positive correlation between two variables, and a PRCC = -1 indicates a perfect negative (or inverse) correlation. The correlation coefficient was calculated based on the rank of each parameter's value rather than on the value itself, because the rank transformations are generally more revealing when nonlinear relationships are involved in a model. A stepwise ranking of each sensitive parameter was then performed to evaluate its relative contribution to the total uncertainty in the dose estimate. For the purposes of this analysis, a parameter was considered sensitive if the absolute value of its partial rank correlation coefficient was greater than 0.50.

The sensitivity analyses were performed for a subset of radionuclides in the grout inventory because the number of parameters that could be varied within each scenario was limited. The driller and post-driller scenario sensitivity analyses included the influence of the grout radionuclide inventory for each of four post-disposal times. The irrigated farm and Columbia River scenario sensitivity analyses were conducted for each significant radionuclide using unit concentrations in ground- or surface water. This approach was used to make the sensitivity analysis for dosimetry parameters independent of the sensitivity analysis for groundwater transport parameters, which was performed separately.

N.2 Intruder Scenarios

The sensitivity analyses for the drilling and post-drilling scenarios will be discussed together because of their similarities (see Appendix M, Exhibit M.1, Section M.0). The parameters that were varied for the sensitivity analysis are indicated in Table N.1. All other parameters were assigned fixed values identical to those used for the deterministic scenario DF evaluations (see Appendix M, Exhibits M.2 and M.3).

In this analysis, it was necessary to define a pre-existing correlation for two of the parameters, the "manual redistribution factor" and the "contaminated area." The "manual redistribution factor" parameter relates the volume of grout exhumed during drilling to the area over which it becomes distributed (see Equation 1). The manual redistribution factor is, therefore, strongly correlated to the "contaminated area" parameter. The definition of a high, but not perfect, correlation between these parameters was desired because of uncertainties in the volume of grout exhumed and the depth of surface soil into which the grout is distributed. The defined correlation coefficient was assumed to be -0.75.

Table N.1. Parameter Values Used for Sensitivity Analysis of the Drilling and Post-drilling Scenarios

Parameter (units)	Scenario	Range of Values			PDF ^(b)
		minimum	central ^(a)	maximum	
Annual soil exposure time (h)	Drilling	24	40	60	U
	Post-Drilling	1000	4383	4383	U
Annual inhalation exposure time (h)	Drilling	0.5	1	10	U
	Post-Drilling	1000	8766	8766	U
Manual redistribution factor (m ⁻¹) ^(c)	Drilling	3.2E-3	6.4E-3	1.3E-2	U
	Post-Drilling	1.3E-4	2.6E-4	6.4E-4	U
Contaminated area (m ²) ^(c)	Drilling	50	100	200	U
	Post-Drilling	1000	2500	5000	U
Daily soil ingestion rate (mg)	Both	50	100	150	T
Mass loading (g/m ³)	Both	1E-5	1E-4	1E-3	U
Fraction of roots in upper soil layer	Post-Drilling	0.75	1	1	U
Above-ground biomass (wet kg/m ²)	Post-Drilling				U
leafy vegetables		1	2	3	
other vegetables		1	2	3	
fruit		1.5	3	4	
Growing time (d)	Post-Drilling				U
leafy vegetables		30	90	90	
other vegetables		30	90	90	
fruit		60	90	90	
Consumption rate (dry kg/y)	Post-Drilling				U
leafy vegetables		2.1	4.1	6.2	
other vegetables		7.0	13.9	20.9	
fruit		3.5	7.0	10.5	
Soil-to-plant concentration ratio	Post-Drilling	0.1	1	10	LU
scaling factor					
Animal transfer factor scaling factor	Post-Drilling	0.1	1	10	LU

(a) The central value indicated for the range is the deterministic value used for the scenario DF evaluation.

Minimum and maximum values indicate the ranges defined for the specified PDFs.

(b) The probability distribution function (PDF) chosen for each parameter range is indicated (U=uniform, T=triangular, LU=loguniform)

(c) Within each scenario, these parameters are defined to be correlated with a correlation coefficient of -0.75.

$$M = \frac{V}{A} \quad (1)$$

where M = manual redistribution factor

V = activity concentration of grout exhumed (Ci/m^3)

A = contaminated area activity concentration (Ci/m^2)

The specific radionuclides evaluated for the drilling and post-drilling scenarios differ because of the different exposure pathways involved in each scenario. Only those radionuclides that contributed greater than 1 mrem EDE based on the deterministic analysis were included in the sensitivity analyses. The radionuclides included in the drilling scenario sensitivity analyses were strontium-90, tin-126, cesium-137, and americium-241. The radionuclides included in the post-drilling scenario were strontium-90, plutonium-239, technetium-99, americium-241, tin-126, neptunium-237, and cesium-137.

Initial sensitivity analysis results (not shown) indicated that time of intrusion was the most sensitive parameter for the drilling and post-drilling scenarios. Because of the high sensitivity of this variable, a second set of sensitivity analyses was run for both the drilling and post-drilling scenarios at each of the 4 post-disposal times evaluated in the deterministic analysis (100, 300, 500, and 1000 years). Elimination of the dominant sensitivity variable by this procedure permitted better discrimination among the sensitivities of the remaining parameters.

N.2.1 Drilling Scenario Sensitivity Analysis Results

The sensitivity analysis results for the drilling scenario are presented in Table N.2. The partial rank correlation coefficients (PRCC) represent the degree to which the ranked value of the associated parameter was correlated with the magnitude of the dose estimate. In addition, a stepwise ranking of the PRCC for each parameter was used to determine its relative contribution to the total uncertainty in the dose estimate. These values are listed under the "Fractional Contribution to Dose Uncertainty" heading in the table and are perhaps more meaningful than the PRCC value itself. The totals listed in this column indicate the fraction of the total uncertainty in the dose that is attributable to the listed parameters. The remaining uncertainty is due to the aggregate of small contributions from relatively insensitive parameters not included in the table.

For reasons described previously, a correlation was defined between the manual redistribution factor and the size of the contaminated area in this portion of the sensitivity analysis (correlation coefficient = -0.75). The PRCC for the manual redistribution factor was consistently higher than that of the

Table N.2. Results of Sensitivity Analysis for the Intruder Drilling Scenario

	<u>PRCC</u>	<u>Fractional Contribution to Dose Uncertainty</u>
100-year Post-disposal		
Cesium-137 concentration in grout	0.94	0.40
Manual redistribution factor/ contaminated area	0.88	0.35
Soil exposure time	0.86	<u>0.17</u>
Total		0.92
300-year Post-disposal		
Cesium-137 concentration in grout	0.91	0.28
Manual redistribution factor/ contaminated area	0.89	0.36
Soil exposure time	0.87	0.22
Tin-126 concentration in grout	0.53	<u>0.03</u>
Total		0.89
500-year Post-disposal		
Tin-126 concentration in grout	0.96	0.40
Manual redistribution factor/ contaminated area	0.93	0.37
Soil exposure time	0.92	<u>0.18</u>
Total		0.95
1,000-year Post-disposal		
Tin-126 concentration in grout	0.97	0.44
Manual redistribution factor/ contaminated area	0.94	0.33
Soil exposure time	0.93	<u>0.19</u>
Total		0.96

contaminated area parameter, and the contaminated area did not meet the criteria for a sensitive parameter at any time period evaluated. For completeness, the sensitivity of both parameters should *qualitatively* be considered together because of their relatively strong correlation. However, the PRCC and contribution to dose uncertainty reported in the tables apply only to the manual redistribution factor.

The drilling scenario sensitivity analysis indicates that the grout radionuclide concentrations generally control uncertainty in the total dose estimate. At 100 and 300 years post-disposal, Cs-137 was the dominant radionuclide, whereas longer-lived Sn-126 became important at the later times. This corresponded to the results for the deterministic analysis, where Cs-137 and Sn-126 were the major contributors to dose

at the early and late post-disposal times, respectively. Other parameters related to the external exposure pathways (soil exposure time, manual redistribution factor, and contaminated area) contributed substantially to the total dose uncertainty as well. It would be expected that the grout radionuclide concentrations should be somewhat less subject to uncertainty than the other parameters related to future events, which are more difficult to predict prospectively. For the drilling scenario, parameters related to the internal exposure pathways (soil ingestion and inhalation) were of low sensitivity relative to the external exposure pathway parameters, which were responsible for more than 89% of the uncertainty in the total dose estimate.

N.2.2 Post-drilling Scenario Sensitivity Analysis Results

The sensitivity analysis results for the post-drilling scenario are shown in Table N.3. As with the drilling scenario, the PRCC and relative contribution to the total dose uncertainty are shown for each sensitive parameter at four post-disposal times.

The results for the post-drilling scenario are similar to those from the drilling scenario, with radionuclide concentrations and parameters related to the external exposure pathways dominating total uncertainty in the final dose. The controlling radionuclide concentrations are the same as for the drilling scenario—Cs-137 at early post-disposal times and Sn-126 at later times. Parameters related to the internal exposure pathways also make minor contributions to the dose uncertainty in this scenario. The ingestion pathway appears to contribute 2-3% to the total uncertainty at early post-disposal times via the soil-to-plant concentration ratio parameter, which determines plant uptake of radionuclides. At the later times, inhalation parameters (exposure time and mass loading of resuspended soil in air) represent a comparable fraction of the total uncertainty. Again, the external exposure pathways are responsible for greater than 85% of the total uncertainty in the dose estimate for this scenario.

N.3 Irrigated Farm and Columbia River Scenarios

The irrigated farm and Columbia River scenarios will be discussed together because of their similarities (refer to Exhibit M.1 in Appendix M for a scenario comparison). In both scenarios, exposure occurs in a family farm environment via the use of radionuclide contaminated groundwater (irrigated farm) or surface water (the Columbia River) for irrigation and domestic purposes. The family farm scenario evaluates dose to an individual, whereas the river scenario considered collective dose to the entire down-river population. Because collective dose in the river scenario is directly correlated with the number of people exposed to radioactive materials in the river, parameters related to the magnitude of the population were not evaluated in the sensitivity analysis. The variable parameters included in the sensitivity analysis, and the assumed distributions of their associated values, are indicated in Table N.4.

Table N.3. Results of Sensitivity Analysis for the Intruder Post-drilling Scenario

	<u>PRCC</u>	<u>Fractional Contribution to Dose Uncertainty</u>
100-year Post-disposal		
Soil exposure time	0.91	0.29
Cesium-137 concentration	0.89	0.26
Manual redistribution factor/ contaminated area	0.86	0.36
Soil-to-plant CR	0.58	<u>0.03</u>
Total		0.95
300-year Post-disposal		
Soil exposure time	0.90	0.27
Manual redistribution factor/ contaminated area	0.87	0.48
Cesium-137 concentration	0.83	0.14
Soil-to-plant CR	0.51	<u>0.02</u>
Total		0.91
500-year Post-disposal		
Manual redistribution factor/ contaminated area	0.84	0.49
Tin-126 concentration	0.82	0.16
Soil exposure time	0.77	0.13
Mass loading	0.67	0.07
Inhalation exposure time	0.61	<u>0.04</u>
Total		0.89
1,000-year Post-disposal		
Tin-126 concentration	0.88	0.25
Manual redistribution factor/ contaminated area	0.87	0.43
Soil exposure time	0.86	0.17
Mass loading	0.57	<u>0.03</u>
Total		0.88

Table N.4. Parameter Values Used for Sensitivity Analysis of the Irrigated farm and Columbia River Scenarios

Parameter (units)	Scenario	Range of Values			PDF ^(b)
		minimum	central ^(a)	maximum	
Annual soil exposure time (h)	Both	1000	4383	4383	U
Annual inhalation exposure time (h)	Both	1000	8766	8766	U
Daily soil ingestion rate (mg)	Both	50	100	150	T
Mass loading (g/m ³)	Both	1E-5	1E-4	1E-3	U
Irrigation application rate (in/y) ^(c)	Farm	16.2	32.4	48.6	U
	River	0	25	32.4	T
Irrigation application duration (mo/y) ^(c)	Farm	1.5	5 ^(d)	6.5	T
	River	0	6.5	6.5	U
Fraction of roots in upper soil layer	Farm	0.75	1	1	U
Above-ground biomass (wet kg/m ²)	Farm				U
leafy vegetables		1.0	2.0	3.0	
other vegetables		1.0	2.0	3.0	
fruit		1.5	3.0	4.5	
Growing time (days)					U
leafy vegetables	Both	30	90	90	
other vegetables	Both	30	90	90	
fruit	Both	60	90	90	
fresh feed	Farm	45		60	
Consumption rate (kg/y)					U
leafy vegetables	Farm	2.1	4.1	6.2	
	River	8.2	17	24.7	
other vegetables	Farm	7.0	13.9	20.9	
	River	27.5	55	82.5	
fruit	Farm	3.5	7	10.5	
	River	17.5	35	52.5	
beet	Farm	11.0	22	33.0	
	River	25.0	50	75.0	
poultry	Farm	2.3	4.6	6.9	
	River	5.2	10.5	15.7	
milk	Farm	25.4	50.8	76.4	
	River	57.5	115	172.5	

Table N.4. (contd)

Parameter (units)	Scenario	Range of Values			PDF ^(b)
		minimum	central ^(a)	maximum	
eggs	Farm	5.3	10.6	15.9	
	River	12.0	24.1	36.1	
fish	River	3E-4	3E-3	3E-2	
drinking water (1/y)	Both	295.0	655	1455	

- (a) The central value indicated for the range is that used in the GENII scenario DF evaluation. Minimum and maximum values indicate the ranges defined for the specified PDFs.
- (b) The probability distribution function (PDF) chosen for each parameter range is indicated (U=uniform, T=triangular, LU=loguniform).
- (c) Within each scenario, the irrigation application duration and rates are correlated with a correlation coefficient of +0.75 for each terrestrial food (leafy vegetables, other vegetables, and fruit), animal feed crop (fresh forage for milk and beef, and stored feed for milk), and the external exposure calculations.
- (d) This value used as the central point of the triangular distribution. The deterministic dose estimate evaluation used 6.5 mo/y as the irrigation duration. The skewed triangular distribution was assumed to best represent the arid region in which the Hanford Site is located.

The farm and river scenarios were evaluated for each radionuclide separately, assuming a unit concentration in ground- or surface water. Only radionuclides that were major contributors to dose in the deterministic calculations were considered for the sensitivity analysis, specifically selenium-79, tin-126, technetium-99, cesium-135, iodine-129, and neptunium-237. In addition, several parameters that were found to be of low sensitivity for the irrigated farm scenario were not evaluated in the sensitivity analysis for the Columbia River scenario. These parameters included the fraction of roots in the upper soil layer, the above-ground biomass for food types, and the growing time for fresh forage for beef and milk. Because of the similarity in exposure pathways for the two scenarios, they were assumed to be relatively unimportant in the river scenario based on the results of the irrigated farm analysis.

Table N.5. Results of Sensitivity Analysis for the Irrigated Farm Scenario

	<u>PRCC</u>	<u>Fractional Contribution to Dose Uncertainty</u>
I-129		
Drinking water consumption	0.96	0.72
Milk consumption rate	0.82	0.11
Milk fresh for. irr. rate	0.64	0.01
Beef fresh for. irr. rate	0.60	0.03
Beef consumption rate	0.55	<u>0.02</u>
Total		0.89
Tc-99		
Drinking water consumption	0.90	0.41
Milk consumption rate	0.84	0.24
Milk fresh for. irr. rate	0.67	0.09
Beef consumption rate	0.64	0.06
Beef fresh for. irr. rate	0.63	<u>0.06</u>
Total		0.86
Np-237		
Drinking water consumption	1.0	1.0
Cs-135		
Drinking water consumption	0.91	0.43
Beef fresh for. irr. rate	0.81	0.15
Beef consumption rate	0.79	0.15
Milk consumption rate	0.60	<u>0.04</u>
Total		0.79
Sn-126		
Beef consumption rate	0.90	0.32
Beef fresh for. irr. rate	0.89	0.30
Drinking water consumption	0.66	<u>0.06</u>
Total		0.68
Se-79		
Drinking water consumption	0.94	0.58
Beef fresh for. irr. rate	0.79	0.11
Beef consumption rate	0.77	<u>0.11</u>
Total		0.80

Table N.6. Results of Sensitivity Analysis for the Columbia River Scenario

	<u>PRCC</u>	<u>Fractional Contribution to Dose Uncertainty</u>
I-129		
Milk fresh for. irr. time	-0.67	0.20
Beef fresh for. irr. time	-0.56	<u>0.17</u>
Total		0.37
Tc-99		
Milk fresh for. irr. time	-0.62	0.07
Milk fresh for. irr. rate	0.55	0.15
Beef fresh for. irr. time	-0.54	0.14
Milk consumption rate	0.52	<u>0.14</u>
Total		0.50
Np-237		
Drinking water consumption	0.88	0.67
Leafy veg irr. time	-0.59	<u>0.09</u>
Total		0.76
Cs-135		
Beef fresh for. irr. time	-0.75	0.40
Milk fresh for. irr. time	-0.54	<u>0.06</u>
Total		0.46
Sn-126		
Beef fresh for. irr. time	-0.88	0.61
Beef consumption rate	0.57	<u>0.07</u>
Total		0.68
Se-79		
Drinking water consumption	1.0	1.0

N.3.1 Irrigated Farm and River Scenario Sensitivity Analysis Results

In contrast to the intruder scenarios, the sensitivity analyses for the irrigated farm and river scenarios were dominated by parameters related to the ingestion exposure pathways (Tables N.5 and N.6). Drinking water ingestion was the only sensitive parameter for Np-237 in the farm scenario, and it controlled the uncertainty in total dose for all other radionuclides except Sn-126. Parameters related to the animal product ingestion pathways (especially beef and milk production) were most significant for Sn-126, and

also contributed substantially to the uncertainty for other radionuclides (except Np-237) in the irrigated farm scenario. The combined contributions to uncertainty for these pathways represented 68 to 100% of the total uncertainty in the dose estimate.

For the Columbia River scenario, uncertainties in the dose estimate were much less sensitive to the drinking water consumption parameter, with the exception of Np-237 and Se-79. For these nuclides, drinking water consumption was the controlling pathway and accounted for 67-100% of the total uncertainty. The leafy vegetable ingestion pathway also contributed a significant fraction of the total for Np-237. For the remaining radionuclides, the dose was most sensitive to the animal product consumption pathways, however in these cases the sensitive parameters represented a smaller fraction of the total uncertainty (less than 70%) than was the case for the farm scenario.

N.4 Irrigated Home Garden

The irrigated home garden scenario considered the consumption and irrigation of crops with contaminated groundwater. The parameters used in the uncertainty analysis for the irrigated home garden scenario are identical to those used in the irrigated farm scenario (see Table N.4), except for the following:

- No animal products were consumed.
- The minimum fruit growing time was 30 days rather than 60 days. The shorter growing time was used to reflect the growth of berries, rather than assuming primarily tree fruit harvests.

The sensitivity analysis was conducted separately on each radionuclide, assuming a unit concentration in groundwater. Only radionuclides that were major contributors to dose were considered for the sensitivity analysis, specifically selenium-79, tin-126, technetium-99, cesium-135, iodine-129, neptunium-237, and uranium-234.

Drinking-water ingestion was the most sensitive parameter of the home garden scenario for all radionuclides, responsible for more than 74% of the uncertainty in the final dose estimate (Table N.7). For uranium-234, the inhalation pathway parameters are also marginally sensitive.

Table N.7. Results of Sensitivity Analysis for the Irrigated Home Garden Scenario

	<u>PRCC</u>	<u>Fractional Contribution to Dose Uncertainty</u>
I-129		
Drinking-water consumption	1.0	1.0
Tc-99		
Drinking-water consumption	0.96	0.92
Other vegetable consumption	0.73	<u>0.03</u>
Total		0.95
Np-237		
Drinking-water consumption	1.0	1.0
Cs-135		
Drinking-water consumption	1.0	1.0
Sn-126		
Drinking-water consumption	0.96	0.74
Soil exposure time	0.92	0.20
Home irrigation rate	0.86	<u>0.05</u>
Total		0.99
Se-79		
Drinking-water consumption	1.0	1.0
U-234		
Drinking-water consumption	0.99	0.99
Mass loading	0.55	0.005
Inhalation exposure time	0.51	<u>0.0025</u>
Total		0.9975

Appendix O

A Conceptual (Qualitative) Description of the Best Estimate Case

Appendix O

A Conceptual (Qualitative) Description of the Best Estimate Case

C. T. Kincaid, Pacific Northwest Laboratory

O.1 Abstract

This is a conceptual description of the best estimate case or perhaps a suite of best estimate cases. This qualitative discussion of how we see contaminants leaving the waste disposal system includes a brief description of the physical setting and general conceptual model, and a brief discussion of exposure pathways to justify the attention given to the subsurface pathway. The majority of the appendix is devoted to a description of the elements or components in this highly engineered disposal system, and to our conceptual model of the occurrence of fluid flow and contaminant transport over the short- and long-term as the engineered system degrades and allows contaminants to release from grout. A brief listing of the initial and boundary conditions complete the qualitative presentation of the best estimate case.

The purpose of this qualitative description is to provide a basis for the development of model parameter values for simulations of the best-estimate case(s) that correspond to the expected performance of the system. Toward that end this appendix describes the role of individual elements in the engineered system. The function each component plays in long-term containment and release is outlined in our discussion of fluid flow and contaminant transport. This conceptual model strongly influences how model parameters for simulating the flow of water and the transport of contamination will be determined.

The major elements of the engineered system described in the appendix are as follows: permanent isolation (Hanford) barrier; RCRA cover, backfill soil; gravel; asphalt barrier; RCRA flow grid, catch basin, and sump; thermal insulation board; steel-reinforced concrete vault; and grout. Future performance of the engineered system is cast in four blocks of time; 0 - 100, 100 - 10^3 , 10^3 - 10^4 , and 10^4 - 10^5 years. Because of the relatively high uncertainty associated with future material properties and the timing and magnitude of degradation, we have chosen to describe the long-term character of the engineered system and the waste it contains in these progressively longer time periods. While arbitrarily assigned, these time periods are the result of increasing uncertainty with increasing time regarding when a given degradation process (e.g., rebar corrosion and seismic stresses) will yield significant degradation to the structural integrity of the system (e.g., through-wall cracking of the concrete vault or asphalt barrier) which leads to a breach in the engineered containment barriers.

This appendix is a record of the consensus achieved regarding the conceptual model for simulating releases and consequences from the disposal of grouted wastes in the proposed engineered system. The next step of selecting and testing submodels and estimating model parameters was not undertaken. Simulations of one or more best estimate cases were not undertaken either. However, this conceptualization provides a valuable basis for understanding the relevance of those conceptualizations and simulations completed and presented in this performance assessment.

O.2 Description of the Physical Setting and General Conceptual Model

The grout waste management area covers approximately $9 \times 10^4 \text{ m}^2$ and the base of vault structures will be 60 to 70-m above the water table of the unconfined aquifer. The 33 vaults containing grouted waste will be paired and placed in rows as shown in Figure O.1. The location of this and other grout program facilities with respect to other Hanford facilities is described in Chapter 2 of the PA.

The PA analysis of the 33 vaults is derived by developing the source term for the saturated zone groundwater model from analysis of an idealized two-dimensional vertical cross section (see Figure O.2) which captures the symmetric half (see Figure O.3) of a pair of vaults located in the vadose zone, i.e., a single vault is analyzed because each pair of vaults shares a single RCRA cover. Two primary assumptions of the conceptual model regarding the substitution of the two-dimensional cross section for the fully three-dimensional field setting are (1) the design and performance of each vault is similar with respect to its engineered systems and its underlying geohydrology, and (2) the flow of water and transport of contamination are predominantly in the vertical direction through the vadose zone and into the unconfined aquifer underlying these vaults. These assumptions are based on our knowledge of the disposal facility and the natural environment in which it has been placed.

Thus, contamination from the 33 vaults moves downward by convection and diffusion to the water table. While the vadose zone that underlies the grout treatment facility is relatively deep, it is assumed the geologic structure or layering is not sufficiently pronounced to result in extensive lateral spreading of contaminants (see Figure O.2). Unlike the 200 West Area which is underlain by the caliche layer, the 200 East Area lacks dominant layering (Lindberg et al. 1992, Appendix C; Fayer and Rockhold 1993, Appendix J) that could result in extensive lateral spreading of contaminants introduced into the subsurface. Therefore, vertical movement of water and contamination is expected to dominate over any lateral spreading.

Conversion of the results from the analysis of a single vault to the field of 33 vaults and the total inventory is achieved by linear scaleup of contaminant flux. Analysis of flow and transport within the vadose zone results in calculation of a fractional release from the unit inventory for the two-dimensional slice of the problem. This fractional release is then applied to the inventory for the entire vault field. This total contaminant flux is then spread evenly over the waste management area as leachate or contaminated recharge to the unconfined aquifer. This calculation does assume that all vaults fail simultaneously.

Figure O.1. Areal View of the Grout Treatment Facility Showing the Location of All Vaults

S9305096 5

Figure 0.2. Two Dimensional Cross Section Showing a Single Vault and the Geologic Cross Section

* The Hanford Barrier will be installed at the end of the postclosure period if required.

S921085.8

Figure O.3. Two Dimensional Cross Section Showing the General Conceptual Design of a Vault Pair that Shares a RCRA Cover

While unlikely in an absolute sense, this is justified in light of the time frames of interest, (e.g., thousands to tens of thousands of years), because failure of vaults and releases of contamination could occur over a relatively short period of time, (e.g., several hundred years).

Contamination arriving at the water table is assumed to enter the aquifer underlying the waste management area as a uniform flux (see Figure O.4). In general, two-dimensional simulation of the vadose zone results in a distribution of point concentrations entering the aquifer. Use of a uniform flux is a necessary simplification resulting from the scale-up process which involves the fractional release (an integrated flux) from the base of the two-dimensional cross-section and the land surface area associated with all of the vaults. This is based on an assumption that lateral spreading or dispersion of contamination in the vadose zone is no greater than the surface area of the waste management area. This incorporates a degree of lateral spreading or dispersion in the estimate of contaminant concentration leaving the unsaturated zone. This assumption also implies that the development of preferential flow and transport paths from individual vaults to the water table is improbable. Clastic dikes have been identified within the grout disposal facility; however, they are not believed to be continuous to the water table. If

Figure O.4. Three Dimensional Schematic Showing the Vertical Projection of the Grout Vaults Onto the Water Table of the Unconfined Aquifer

they are found to extend to the aquifer, they could represent a preferential flow path. If present, preferential pathways for individual vaults would result in different estimates of flux (e.g., earlier) and point concentrations (e.g., higher) leaving the unsaturated zone and entering the aquifer; however, the effect on overall release from all vaults is assumed to be small.

O.3 Description of the Exposure Pathways

Exposure pathways provide a route for the radioactive waste to come into contact with the biosphere and human beings. It is important to briefly describe scenarios which identify some of these exposure pathways that involve groundwater because our simulations of the unsaturated zone and unconfined aquifer provide input necessary for these scenarios. We are analyzing the potential health threat posed by contaminated groundwater. Several scenarios are examined which are based on the use or consumption of contaminated water; e.g., groundwater as a water source for drinking water, for irrigating a garden, for irrigating a family farm, and water from the Columbia River downstream of the site for both a domestic water supply and a source of irrigation water. An intruder scenario is also included which addresses the threat to human health posed by exhuming the radioactive waste. Greater details on these scenarios can be found in the text of the PA in Chapter 1 and Section 3.3.4.4. Knowing how model simulations are to be used will be a factor in determining the output requirements of analyses. Note that exposure pathways are fixed and not varied throughout the analysis.

O.3.1 Drinking Water Scenario

Only the drinking water exposure pathway is considered in the drinking water scenario. For this scenario the limits established for drinking water have been applied to water pumped from a downgradient well. The performance objective adopted by the grout program for this scenario is a maximum allowable dose received from drinking 2L/d of water. This objective is based on a proposed EPA regulation which allows a 4 mrem/yr effective dose equivalent to the individual who consumes 2L/d of drinking water. Doses for this scenario will be based on a water consumption rate of 2 L/d and the ingestion dose factors recommended by DOE (U.S. DOE 1988b).

O.3.2 Irrigated Garden and Irrigated Farm Scenarios

For the irrigated garden and farm scenarios, all pathways of exposure are considered. A performance goal of 25 mrem/yr effective dose equivalent for all radionuclides to the maximally exposed individual will be used. This is consistent with DOE Order 5820.2A (U.S. DOE 1988a), proposed EPA regulations (proposed 40 CFR 191, see 58 FR 7924; also see Gruhlke, Galpin and Holcomb 1989), and existing NRC regulation (10 CFR 61).

O.3.3 River Scenario

The river scenario is also an all-pathways exposure scenario which evaluates dose to the collective downriver population. Contaminants transported to the river by groundwater are assumed to be mixed in the total river volume, and the water is used for domestic, agricultural, and recreational purposes by the downstream population. Results of the river scenario are anticipated to indicate very low doses to the public because of the large flow of the Columbia River and the low flux of contaminated groundwater. If results of the irrigated farm scenario easily satisfy the all-pathways dose limit of 25 mrem/yr, an integrated population dose should be calculated for the river scenario.

O.3.4 Intruder Scenarios

For these scenarios, an intruder is assumed to drill a well directly into the grout, thus bringing contaminated material to the surface. An individual is then assumed to establish a residence at the site and to use the area for limited agricultural purposes. The performance goal is a maximum dose for continuous exposure to the resident of 100 mrem/yr. The performance goal for dose to the driller is a maximum total dose, including committed dose received over 50 years following a one-time exposure, of 500 mrem. The disposal system incorporates passive controls designed to warn and deter inadvertent intruders for at least 500 years after disposal. Thus, intruder doses will be calculated for 100, 300, 500, and 1,000 years, but compared to the intruder scenario performance goals 500 years after disposal.

O.4 Description of Elements in the Conceptual Model of the Engineered System

Elements of the original engineered system and its surrounding environment were described in Chapter 2 of the PA. Schematic drawings of the two-dimensional structure are shown in Figures O.3 and O.5. The role of individual elements of the engineered system in the current design is described below. Then the long-term containment/release function of each component for this best estimate case is outlined. Our conceptual model is the description of how the system is envisioned to function and degrade in the long term. The conceptual model provides the rationale for choosing model parameters to approximate the flow of water and transport of contamination.

While material science provides insight into the expected long-term changes in material properties, long-term forecasts of how an engineered structure containing a waste form will perform are highly uncertain. This is largely because materials will be used in the engineered system for which only a short record of performance exists; e.g., the Portland cement being used to construct the primary containment structure has only been in use for approximately a century, the asphalt being used to construct a combined convection-diffusion barrier is a separated fraction from a natural petroleum with a short performance history, and the high-density polyethylene (HDPE) material used in the RCRA drainage net and liners has only a 35 year performance record. While the performance of materials such as Portland cement and

Figure O.5. A Schematic Drawing (two-dimensional vertical cross section) Showing Different Elements of the Engineered Disposal System, and an Exploded View of the Drainage Net and Thermal Insulation Barrier

asphalt pavement is well documented for structures that are above ground (e.g., bridges, building, highways), little information exists about the performance of these materials below ground. Uncertainty in forecasts are also a result of the rather near-term focus of the structural design (i.e., a design or service life of less than 100 years). As a result materials selection and engineering design are not directly related to long-term performance. For these reasons, we have chosen to describe the long-term character of the engineered system and the waste it contains in progressively longer time periods, i.e., 0 - 100, 100 - 10^3 , 10^3 - 10^4 , and 10^4 - 10^5 years. While arbitrarily assigned, these time periods arise because of the increasing uncertainty with increasing time regarding when a given degradation process (e.g., rebar corrosion and seismic stresses) will yield significant degradation of the structural integrity of the system (e.g., through-wall cracking of the concrete) that in turn leads to a breach in the engineered containment barriers. If peak doses are not predicted within the 10^5 year period, or if longer term secondary peaks are of interest, the simulations should continue indefinitely to be based on the degradation state at the close of the final period.

A brief description of each of the major elements of the engineered system shown in Figures O.3 and 5 follows.

O.4.1 Hanford Unconfined Aquifer

If there is a single case developed for "best estimate" it needs to be an irrigation based scenario. This is the only scenario that will match land-use planning documents and match the irrigated farm and garden all-pathways scenarios. If several cases are developed, they could examine alternate land-use scenarios, e.g., a long-term dormant site or non-irrigated state resulting in long-term 0.1 cm/yr recharge.

O.4.2 Protective (Hanford) Barrier

Located at the soil-atmosphere boundary, this element of the engineered system acts to recycle annual precipitation to the atmosphere by storing it in 1.5 to 2-m of silt-loam soil until evapotranspiration can remove the water during the growing season for both shallow and deep rooted vegetation. The details of this element of the engineered system are not modeled directly in our simulation of the vadose zone. Rather, the results of the research program studying protective barriers have been used to estimate a maximum average annual recharge that could occur through the protective barrier (design objective 0.05 cm/yr). Gee et al. (1992) reported the results obtained on the 200 Area Plateau at the Hanford Site from lysimeters containing silt loam. Lysimeters that were exposed to two times (2X) normal precipitation from 1987 through 1990 produced no drainage regardless of the presence or absence of plants. Unpublished data from continued monitoring of these lysimeters which have since been exposed to three-times (3X) normal precipitation reveal no drainage from vegetated lysimeters but drainage through lysimeters maintained free of vegetation. For the best estimate case a 0.1 cm/yr annual average recharge rate is assumed to apply based on the existing research; this is conservative with respect to both the reported research and the design objective of the isolation barrier program.

It is not uncommon for questions to arise regarding the response of waste disposal systems to a greater recharge rate. Greater recharge could be a consequence of a variety of future events, e.g., climate change arising from changes in greenhouse gases or the onset of the next ice age, unforeseen degradation of the protective barrier system, or future agricultural land use resulting in irrigation on the Hanford Site and directly over the waste disposal units. Note that the design life of the protective barrier system is 1,000 years; however, features such as the gravel admix included in the upper soil layer to prevent excessive wind erosion should enable the barrier to function indefinitely. Historically, the possible effects of greater recharge have been examined by analyzing system response to a uniformly applied 5-cm/yr recharge rate (U.S. DOE 1987, Appendices O, P, and Q). In this PA we will examine the potential impacts of greater recharge by simulating the effects of an increase of 5-cm/yr of recharge uniformly superimposed on present-day recharge for the entire Hanford Site. This will be an envelop or sensitivity case (i.e., not the best estimate case) which quantifies the potential impact of higher recharge.

O.4.3 RCRA Cover

This cover is located between the base of the protective barrier and upper surface of the asphalt barrier. Its purpose is to limit the rate of recharge moving vertically and directly contacting the asphalt barrier and the engineered structures containing waste. The design requirement for saturated hydraulic conductivity, K_{sat} , of the RCRA cover is less than or equal to 1×10^{-7} cm/s (3 cm/yr). It is composed of a mixture of two natural materials; fine soil and clay. The mixture and its field placement will be tested to assure compliance with the K_{sat} requirement. The RCRA cover has a design or service life of 30 years. However, it is composed of natural materials, and, in the vadose setting at the Hanford Site, it may retain its unsaturated hydraulic properties and function as designed indefinitely. That function will limit direct infiltration contacting the waste disposal system to a maximum of 3 cm/yr. In the nominal case of continuous 0.1 cm/yr recharge, virtually all of the recharge moves through the RCRA cover. However, in the high recharge case (≈ 5 cm/yr), the RCRA cover limits direct recharge to 3 cm/yr and redirects the additional infiltration to the right side of the modeled cross section (see Figure O.2).

O.4.4 Backfill Soil

Construction of the waste disposal system occurs in an excavation. The vault and its surrounding engineered system is entirely buried when completed. Excavated soil is stored and later used to backfill around and above the engineered structure. Soils from the excavations for the first five vaults were sampled and characterized for use in these simulations.

O.4.5 Gravel

Gravel appears twice in the design. A wedge of gravel is placed immediately above the asphalt barrier, and a layer of gravel is placed in the catch basin. Specifications call for the gravel to be washed and sieved before placement to remove fines and large rock. Thus, it is uniform and clean, and as a result its hydraulic characteristics in an unsaturated environment are distinctly different than those of a common gravel or soil. While such a gravel has a relatively high saturated hydraulic conductivity because of its

open porosity, it acts as a barrier to water flow in the unsaturated zone because of its relatively low unsaturated conductivity and its relatively high (near zero) air entry potential. Thus, given any alternative drainage route requiring lower saturations, water in the surrounding media will move around the gravel (Jury et al. 1991, pp. 110-112). Methods for placing the gravel and overlying material will ensure the integrity of this layer. Gravels with substantial open porosity have existed in the Hanford formation sediments for thousands of years. Therefore, the hydraulic properties of the gravel layer are assumed not to degrade over time.

The saturated and unsaturated properties of gravel were central to the use of gravel in the waste disposal system design. Its saturated hydraulic properties were the dominant consideration in its selection for the use as a filler for the catch basin. If a leak occurs in the walls or floor of the steel-reinforced concrete vault during the first 30 years, it is important to route the contaminated solution to a sump and remove it from the system. A leak implies a liquid release from the grout through the concrete vault in sufficient quantity to cause saturated conditions in the RCRA flow grid (a required RCRA drainage network described in subsequent paragraphs) resulting in drainage to the catch basin. The saturated hydraulics of the uniform and clean gravel in the catch basin cause the contaminated water to flow to the drain and sump for removal.

The unsaturated hydraulic properties of gravel were a consideration in the decision to place a wedge shaped layer of gravel above the asphalt barrier. The gravel wedge will be overlain by unsaturated filter sand. Pressure of the water phase in the overlying unsaturated sand must approach the air entry potential of the gravel medium before water will move into the gravel. The air entry potential of the uniform and clean gravel is high (i.e., very near atmospheric pressure or zero), and water in overlying or adjacent sand deposits must come nearly to full saturation before such a pressure is reached or exceeded. Because filter sand is composed of fine soils (low air entry potential) and these same fines are absent from the gravel (high air entry potential), water infiltrating through the RCRA cover will be routed to the right side of the waste disposal system (see the modeled cross section in Figure O.3) in the filter sand rather than allowed to drain through the gravel wedge.

O.4.6 Asphalt Barrier

An asphalt barrier^(a) at least 1-m thick completely surrounds the vault, catch basin, and sump.^(b) Asphalt has three attributes that impact disposal system performance; water does not wet asphalt, wetting is retarded by an asphalt coating, and asphalt has a low diffusion coefficient. The asphalt barrier contains more asphalt and has lower air void space than standard asphalt pavement used in highway and road construction. Thus, its wettability and diffusion properties combined with the asphalt and air content specifications provide a material that should minimize the convection of liquid water and control the diffusion of contaminants.

The asphalt barrier has been analyzed for degradation. However, the common experience of most people, that of watching streets, roads, and highway systems made of asphalt pavement degrade, does not apply directly to the asphalt barrier used in this waste disposal system. The dominant processes leading to the degradation of the much lower quality and thinner asphalt pavements are direct exposure to daily and seasonal cycles of heat and cold, freeze and thaw, sunlight, and traffic loads. Contrast this with the thick and high quality asphalt barrier of the waste disposal system which is buried and not exposed to sunlight, climatic cycles, or traffic loads.

Processes anticipated to cause asphalt barrier degradation are summarized as follows (see Appendix Q):

<u>Process or Mechanism</u>	<u>Associated Degradation</u>
<ul style="list-style-type: none"> • oxidation of asphalt 	<ul style="list-style-type: none"> • Oxidation will initiate at the surfaces of the asphalt barrier. The bulk of the asphalt in the barrier will oxidize over time. This mechanism will contribute to the brittleness of the barrier.

-
- (a) The design specification for the asphalt barrier calls for an asphalt content of $7.5 \pm 0.5\%$ by weight of the total asphalt mixture. Aggregate pretreated with an anti-stripping additive will therefore comprise $92.5 \pm 0.5\%$ by weight of the total. Placement specifications call for compaction to a minimum 96% of maximum density, and to less than 4% by volume of air void (Kaiser Engineers Hanford Company 1989).
- (b) There is 0.46-m (18 inches) of asphalt barrier overlying 0.46-m of asphalt-coated gravel which form the base of the first four vaults (218-E-16-102 through 105). The remainder of the vault structure is enclosed by 1-m of asphalt barrier. Each of the remaining 29 vaults will be constructed with a complete 1-m asphalt barrier surrounding the entire structure.

- volatilization of asphalt
 - age hardening of asphalt
 - flow and creep of asphalt
 - thermal board disintegration
 - short-term seismic stresses
 - long-term seismic stresses
 - thermal stress
 - construction joint weakness
- Volatilization will probably happen early in the life of asphalt and will result in increased brittleness. The impact of volatilization on the flow or creep properties of asphalt will depend largely on the thermal environment the barrier experiences after placement, i.e., grout cure and radiolytic heating.
 - Age hardening and polycondensation reactions affect the bulk properties of asphalt and will result in an increase in brittleness. This phenomena could have a significant impact on crack formation in the asphalt barrier. The rates tend to slow with time but at some point can inhibit the crack healing processes because of decreasing ability of the asphalt to flow or creep.
 - Based on the above processes that increase brittleness, one subjective estimate is that the barrier will tend to flow and creep for up to 100 years. However, flow and creep behavior is expected to constantly decrease and not occur after 100 years.
 - Cracks (5-mm; horizontal and vertical) in the wall-roof joint area; caused by slumping of the asphalt barrier wall in response to thermal board disappearance.
 - No cracks; because the probability of significant seismic loading is low in the near term and the asphalt is relatively ductile.
 - Cracks will be extended or initiated in the hardened or embrittled asphalt and this will accelerate hardening of the overall cross section of asphalt. Asphalt hardening should be a surface phenomena.
 - No cracks; because thermal stresses are highest in the first 300 years and the asphalt should be relatively ductile, reducing the probability of thermal cracking; (thermal events are summarized in the section on thermal insulation board).
 - No cracks; because the surface preparations and the healing nature of fresh asphalt are expected to make this weakness insignificant; this expectation of cold joint strength was partially confirmed in tensile testing

- biodegradation
- Biodegradation of exposed surfaces has been confirmed with a measured value for AR-6000 asphalt of 1.17×10^{-4} cm/yr (Luey and Li 1993) after 310 days in contact with wet (70% saturation) soil; it is postulated that the increased surface area exposed by cracks could accelerate the biodegradation and result in increased effective size of cracks; a rate of 1×10^{-4} cm/yr is a best estimate of actual long-term biodegradation in relatively dry soils. Biodegradation is a surface phenomena and it is anticipated that the rate of biodegradation will decrease over time. We also do not anticipate the barrier "disappearing;" instead we expect the asphalt to exist beyond 100,000 years.

The asphalt barrier will be buried in a dark and humid soil environment where biodegradation of exposed asphalt surfaces by microorganisms can occur. In addition, the asphalt may lose its elasticity with time as some components responsible for the elastic and ductile character of the asphalt volatilize and escape the asphalt concrete during the initial 300 year period associated with grout cure and radioactive decay. The resulting embrittlement of the asphalt, when combined with the magnitude of potential seismic events over very long time periods (e.g., 10^3 - 10^5 years), results in an increasing potential for the asphalt barrier to develop through-wall cracks forming a grid pattern on all asphalt surfaces (i.e., top, sides, and base).

O.4.7 RCRA Flow Grid, Catch Basin, and Sump

A RCRA requirement for double containment is satisfied by these elements of the disposal system design. The flow grid or drainage net (see Figure O.5) is composed of high-density polyethylene (HDPE) strands bonded or cast to form a mesh a minimum of 5-mm thick. Two sheets of flow grid (total minimum thickness of 1-cm) are placed on the outer surface of the reinforce-concrete vault. This is followed by a 60 mil (1.5 mm) HDPE curtain and a layer of geotextile. The flow grid is designed to direct any flow of liquids that might escape from the grout through the steel-reinforced concrete vault to the catch basin which underlies the vault. The basin is filled with uniform, clean gravel described above. Flow from the basin drains to the sump which will be pumped to remove any drainage from the vault during the first 30 years of vault service. The real function of this component of the engineered system is to contain and capture liquids until the grout has set and free liquid is removed; a period of time measured in months.

This RCRA system is designed to have a service life of 30 years because of the regulatory requirements under RCRA. It is assumed that it will function as a preferred path for any leachate from the waste disposal system for a much longer period of time. HDPE material should be chemically inert in the grout vault environment, even in the presence of radiation. Radiation exposure causes crosslinking of polymer chains which results in reductions in break strength and break elongation. These effects occur in the Mrad (10^6 rad) range, and become most pronounced at doses of 16 to 37 Mrad. However, location of the

flow grid and curtain outside the concrete wall reduces the dose to about 14 rad. This dose will not have any effect on the HDPE material. Although HDPE materials have only been in existence for about 35 years, plastics experts (e.g., N.R. Gordon, a plastics expert with PNL) believe that properties of HDPE should change very little, even for thousands of years. The only significant physical modification envisioned is some reduction of the flow net thickness (originally 1-cm) because of the viscoelastic (creep) response to external pressures. As is noted in the following description of reinforced concrete, forces originating in the corrosion of steel reinforcement may impact the flow path material but not the overall conclusion that a vertical flow path will exist along the walls of the vault for thousands of years.

The catch basin is composed of reinforced concrete and it is assumed it will degrade as the reinforced-concrete vault is forecast to degrade. Relative movement between the drainage basin and sump pit should be minimal due to the robust structural interface connecting the two structures, e.g., the interface is constructed of reinforced concrete and its thickness reaches 4.572-m (15-ft) (see Figure O.6). A 26 inch outside diameter riser made of carbon steel connects the sump to the land surface. This riser protrudes through the asphalt barrier above the sump. Initially, the sump is filled with gravel to provide volume stability. During closure of the facility, the riser and sump are to be backfilled with a grout slurry. Corrosion of the carbon steel may provide a release pathway if saturated conditions were to exist in the catch basin and sump, and if the asphalt barrier continues to act as an impermeable barrier, (i.e., if the asphalt barrier presents a perfect 'bath tub' situation). It is not envisioned that the basin and sump will function in this way; rather, that liquid under positive pressure (saturated ponding in the catch basin and sump) would drain through the intact or degraded engineered system before significant levels of ponding could occur within the structure.

O.4.8 Thermal Insulation Board

In addition to the 1-cm (minimum thickness) flow net, there is a 2.54-cm (1-in) minimum thickness layer of relatively porous thermal insulation board. This material is placed between the flow-net/HDPE curtain/geotextile and the asphalt barrier as illustrated in Figure O.5. It insulates both the steel-reinforced concrete and the HDPE materials from the thermal shock of the asphalt barrier material when it is placed during construction.^(a) An estimate for the disintegration of this wood-based material is based on knowledge of wood disintegration in the anticipated environment (asphalt coated, low moisture, low air availability). The best estimate is that a slow disintegration will occur. The disintegration of this material is

-
- (a) Specifications (Kaiser Engineers Hanford Company 1989) for the asphalt barrier call for the mix temperature to not exceed 171°C (340°F) at the batch plant, to be not less than 126.5°C (260°F) at the rear of the laydown machine during placement, and to be not less than 88°C (190°F, average lift mix temperature) before roller compaction is completed. Data collected during placement of the asphalt barriers around vaults 218-E-16-102 through 105 demonstrated that placement temperature was between 143.5 and 149°C (290 and 300°F). Design specifications for the grout formulation call for grout cure to occur at or below 90°C. Estimates of grout temperature resulting from the decay of radionuclides indicate a broad temperature plateau of approximately 55°C (131°F) for a 35 to 50 year period followed by a gradual decline to ambient temperatures after 200 to 300 years.

(a) Vertical cross-section of basin-sump connection

(b) Plan view of basin-sump connection

S9211085.50

Figure O.6. Schematic Drawing Showing the Reinforced-Concrete Structure Connecting the Sump to the Catch Basin

forecast to occur in the 100 to 1,000 year time period. Disintegration of this material will lead to either the formation of a void between the flow net and asphalt barrier wall, or to the gradual and continual compression of the thermal board in response to external loads. In either case, it is anticipated that slumping of the ductile asphalt barrier wall into the space previously occupied by high-integrity thermal insulation board will be sufficient to induce cracks in the vicinity of wall-roof joints of the asphalt barrier.

O.4.9 Steel-Reinforced Concrete Vault

The vault, catch basin, and sump enclosure are all constructed of steel-reinforced concrete. For the grout vault geological environment no near-surface faults nor soil liquefaction potentials have been identified and the potential for seismic stresses to affect the buried structure are low. This was demonstrated by a 0.35g three-dimensional seismic evaluation of a symmetric quarter of the vault in its final configuration, i.e., filled with grout, (B. V. Winkel, 1992, private communication^(a)).

The processes anticipated to cause reinforced-concrete material degradation are summarized as follows (see Appendix Q):

<u>Process or Mechanism</u>	<u>Associated Degradation</u>
• short-term seismic stress	• A three-dimensional symmetric quarter of the vault was analyzed for a 0.35 g acceleration event and it demonstrated negligible impact on the design structure.
• long-term seismic stress	• Extension of partial cracks and creation of through cracks in the aged and rebar corroded reinforced-concrete structures.
• short-term rebar corrosion	• Short term rebar corrosion is unlikely because of 1) cathodic protection, 2) high pH level, 3) low permeability of concrete, 4) relatively low chlorides, and 5) presence of asphalt liner separating grout from concrete vault.
• long-term rebar corrosion	• Loss of integrity of reinforcing steel and the associated susceptibility to seismic load failure, and localized cracking of the concrete surface adjacent to rebar and the associated change in hydraulic characteristics of concrete surfaces.
• overburden loads	• Cracks in unreinforced roof plank joints.

(a) Winkel, B. V. 1992. "Grout Vault Asphalt Barrier Seismic Adequacy, Preliminary Report." Memo from B. V. Winkel to R. K. Sanan, BVW-23420-92-001, April 21, 1992.

- corrosion of water stops
- short-term drying shrinkage
- short-term thermal stress
- chemical reactions
- Cracks at construction joints in walls and floors.
- Relatively tight cracks limited to the surface caused by the different drying rates of exterior and interior concrete.
- Tight cracks on the surface of the concrete are produced by relatively high thermal stress levels resulting from high thermal gradients caused by heat of hydration during grout cure and cesium decay.
- While some long-term chemical degradation is likely, the consequences should be minimal because chemical degradation reaction products will tend to bond to the concrete and fill cracks, and relatively few pore volumes of potentially chemically degrading waters are anticipated to flow through the structure. Some resealing is expected in seismically-induced crack openings.

The above listed mechanisms and processes will take their toll over the extended life of the waste disposal system (i.e., 10^5 years); however, the reinforced-concrete structure is assumed to exhibit relatively high integrity for 1,000 years. This level of assumed integrity is a result of the initial integrity and volumetric stability of the structure, the fact that it is buried and thus isolated from the environmental extremes, and the alkaline character of the wastes. A principal mechanism leading to the degradation of the integrity of the reinforced-concrete vault is the corrosion of the reinforcing steel and waterstops caused by the advection and diffusion of waste constituents to the steel surfaces. While unable to quantify the long-term performance of the asphalt liner inside the vault, one should recognize its presence and the role it will play in impeding the migration of contaminants to the steel.

Two classes of cracks are apparent in the preceding description of processes and associated degradation; surface cracks and through-wall cracks. Cracks are anticipated to occur on all concrete surfaces in response to rebar corrosion. Degradation of these surfaces could result in the creation of preferential flow paths from a saturated flow perspective, and in the creation of capillary breaks or barriers to flow from the unsaturated flow perspective. However, the interior portion of the concrete wall (i.e., concrete between the interior and exterior rebar mesh) should retain its original high integrity and low hydraulic conductivity. Releases will not occur solely because of surface cracks. On the other hand, once through-wall cracks appear, they may represent conduits for the release of contaminated liquid from the grout through the reinforced-concrete vault.

With the exception of the joints between roof-plank sections the structure is assumed to function as designed for 100 years. During the 100 to 1,000 year period additional degradation of the roof-plank joints is assumed to be accompanied by degradation of construction joints and the onset of concrete surface degradation resulting from rebar corrosion. In addition to greater degradation of joints and concrete

surfaces, through-wall cracks induced by rebar corrosion and seismic events are forecast to appear during the 10^3 to 10^4 year time period. During the final time period (10^4 to 10^5 years) which represents the indefinite future for the PA analysis, cracks existing after 10^4 years become wider (e.g., 2-mm) and through-wall cracks caused by rebar corrosion and seismic events become more closely spaced (e.g., 0.5-m square grid).

0.4.10 Grout

A considerable and continuing effort exists regarding the formulation of grout and the measurement of its original properties. Standard methods have been used to determine the leachability of a variety of grout formulations and the unsaturated hydraulic properties of a single sample. However, the long-term hydraulic, transport, and attenuation properties of the grout are an area of considerable uncertainty. During the curing process for grout, a cementitious material with a high porosity (55 to 60 % by volume), a very fine pore structure, and continuously connected pore space is formed. While grout cures and excess liquid is removed in a matter of months, the actual curing process continues indefinitely, and, in general, the hydration products of the cement and fly ash continue to be formed, (i.e., hydrated calcium silicate and calcium hydroxide). During hydration, the hydrated cement gel material incorporates pore water and forms precipitates on the surfaces of existing solids that border the pores. Thus, the pore structure will become finer with time as the curing process continues to form hydration products (Dames and Moore 1989).

Care is taken in formulating grout to minimize the potential for formation of expansive minerals that could cause extreme internal stresses and cracking. The formulation efforts attempt to minimize the depletion of OH and the formation of gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) within the grout. Infiltrating water may import sulfate into the concrete and grout materials; however, sulfate concentrations in water (Dames and Moore 1989) contacting Hanford soils are below concentrations associated with the formation of significant amounts of expansive minerals.

Grout is designed to exhibit relatively good volume stability indefinitely; however, it is not designed to develop the compressive strength and other structural properties of concrete. Consequently, the grout could degrade as the reinforced-concrete vault degrades and external (e.g., seismic) loads are transferred to the grout monolith. Because it will not have sufficient structural strength to bear these loads, it is anticipated that the grout monolith will experience cracking, fracturing, or a generalized breakup in response to vault degradation. (i.e., the timing of grout degradation may correspond to the timing of steel-reinforced concrete vault degradation). The severity of such a degradation process (i.e., timing and magnitude) and the uniformity of associated cracks are unknown and have not been forecast from first principles. However, the grout monolith could experience stresses at points where the vault experiences through-wall cracks because of the inability of the vault structure to bear loads at these locations. It is possible that localized crushing would occur at locations directly opposite corroding rebar and that crushing would be limited to the grout surface. These weakened regions on the grout monolith could then be impacted by seismic loadings, and extensive cracks could form. Thus, as a first approximation, one could assume the grout monolith cracks along planes defined by construction joint cracks in the

reinforced-concrete vault. This would imply 3 cracks in the walls creating 3 horizontal cracks, 1 crack in the floor creating a vertical crack in the center of the cross-section, and 2 cracks crossing the longitudinal axis of the vault (see Figure O.9). Thus, the vertical cross section would include 8 blocks, while the entire monolith would include 24 blocks.

Because of the composition of Hanford soils, natural infiltration percolating into the vault and grout waste form through fine cracks is anticipated to carry with it dissolved carbon dioxide (CO_2). The pH of the infiltrating water will be nearly neutral, but upon reaching either the concrete or grout, the high pH pore fluids will cause the CO_2 to react with CaOH and precipitate calcium carbonate (CaCO_3) abruptly in pores or cracks which conduct the infiltrating waters. This mineral precipitation could cause plugging of cracks at high pH interfaces, or a more general filling of cracks along crack surfaces.

Infiltrating water from the surrounding soil environment is expected to be imported in limited quantities. Thus, infiltrating water is expected to affect only a small portion of the grout monolith. Typically, impacts are anticipated at the outer surface of the grout where infiltrating waters bearing dissolved CO_2 first contact the grout as a result of convection and diffusion processes, and in the cracks of the monolith where waters may preferentially flow and diffuse. These impacts will likely be limited to the vicinity of breaks in the concrete and asphalt barrier which provide the pathway for the infiltrating water and chemicals to convect and diffuse to the grout surfaces and cracks. Note that portions of the grout monolith characterized by the discharge of pore water to the surrounding engineered system should not be associated with the precipitation of calcium carbonate, but should be associated with the formation of hydration products. If grout pore water reaches the vadose sediments with its high pH intact, calcium carbonate could precipitate in the sediments.

The overall long-term conceptual model is one of a fractured grout monolith; its matrix made up of blocks of unfractured grout, and its fractures or cracks partially or completely plugged with calcium carbonate or hydration products (hydrated calcium silicate and calcium hydroxide). The continuing formation of hydrated calcium silicate and calcium hydroxide during long-term grout cure should result in a finer pore structure with time in blocks of unfractured grout. Thus, the unsaturated hydraulic performance of the unfractured grout would be conservatively modeled using the original (i.e., freshly cured) unsaturated hydraulic properties measured for grout. The true hydraulic performance of the fractures will depend on the pore structure associated with the fracture openings. A number of alternatives exist, e.g.,

- cracks are open and represent a discontinuity in the unsaturated material,
- cracks are plugged at points where infiltrating waters contact them, (e.g., at the pH front), and open elsewhere,
- cracks are filled throughout their volume with calcium carbonate as a result of complete contact with infiltrating water.

- cracks are filled with hydrated calcium silicate and calcium hydroxide formed during long-term cure of the adjacent unfractured grout block, or
- cracks are filled with a combination of calcium carbonate at exterior surfaces, and hydrated calcium silicate and calcium hydroxide on interior surfaces.

Based on our knowledge of the chemistry of grout, and, in particular, the long-term character of its curing process, it is assumed that minerals do form in cracked grout. These minerals are deposited in cracks, and can be envisioned as either fine grained deposits of calcium carbonate along crack surfaces where waters of different pH would contact one another, or as fine grained deposits of hydrated calcium silicate and calcium hydroxide formed on grout surfaces that border cracks. As a result, the crack surfaces will likely be coated, if not filled, with fine mineral deposits.

0.5 Description of Changes in the Conceptual Model with Time

On the basis of the level of uncertainty in future material properties and in the timing and magnitude of degradation of engineered materials, we have chosen to describe the long-term character of the engineered system and the waste it contains in four (4) progressively longer time periods, i.e., 0 - 100, 100 - 10^3 , 10^3 - 10^4 , and 10^4 - 10^5 years. The identification of distinct time periods for the simulation of degraded materials is also justified on the basis of existing modeling capabilities. State-of-the-art codes generally consider constant material (e.g., hydraulic, transport) properties and time varying boundary conditions. Such codes can be applied in a step mode; properties are held constant for each time interval and careful attention is given to ensure a stable and mass conserving simulation following changes to material properties. The paragraphs that follow are based on the previously described degradation of individual elements in the engineered system. They present the way it is envisioned that elements of the system will work as a whole, and how that will change with time.

0.5.1 Conceptual Model of the 0 - 100 Year Period

During the first 100 years the grouted waste and surrounding engineered system is assumed to function as designed. For example, if a grout vault leaks in its first 30 years of operation, it is assumed the leaked fluid will be routed by the flow grid or drainage net to the gravel-lined catch basin, by the 4-inch drain to the sump, and then be removed by pumping for further treatment and disposal. It is assumed that any significant degradation of the waste disposal system during the first 100 year period of institutional control would be detected by surveillance or monitoring programs and corrected.

Degradation during this period is anticipated to be limited to surface biodegradation of the asphalt barrier at the soil-asphalt interface, and cracking at roof plank joints (see Figure O.7). The rate of biodegradation is assumed to be approximately twice the rate described previously for AR-6000 asphalt, (i.e.,

(a) End view cross-section of vault.

(b) Schematic of roof plank joint orientation and distribution

S9211085.52

Figure O.7. Schematic Drawing Showing the Degradation During the 0 - 100 Year Period, and an Exploded View of Roof-Plank Joint Orientation and Distribution

$2 \times 1 \times 10^{-4} \text{ cm/yr} = 2 \times 10^{-4} \text{ cm/yr}$). Roof plank joints run the width of the vault and are composed of unreinforced grout covered by a thin layer of concrete. They are assumed to be cracked by overburden loading.

Despite this minor cracking of an interior component of the engineered system, the overall system retains its high integrity and does not allow the convection of waste to the soil environment because the original 1-m thick asphalt barrier has not cracked. Isolated from the surrounding soil environment by the hydrophobic asphalt barrier, the fully saturated grout undergoes a temperature pulse (90°C) during cure and experiences heat generation and temperature buildup (55°C) by radioactive (cesium) decay. The interior of the vault has an asphalt coating which should eliminate or make negligible any leakage during this initial 100 year period. The grouted waste is assumed to function as an intact monolith during this period even if thermal and shrinkage cracks develop.

O.5.2 Conceptual Model of the 100 - 10^3 Year Period

It is anticipated that degradation after 100 years will have a minor but recognizable effect on the integrity of the engineered system by the end of the 100 to 1,000 year period. Note that the size and spacing of cracks described below are end-state descriptions, and should not necessarily be associated with the beginning of the time period.

The asphalt barrier is degraded in two ways during this time period; 1) horizontal and vertical cracks (5-mm) caused by the disintegration of the thermal insulation board and slumping of the asphalt barrier walls (see Figure O.8) appear in the upper corners, and 2) biodegradation takes place on the interior and exterior surfaces of the asphalt barrier, and on the crack surfaces of the asphalt barrier. Cracks in the asphalt barrier are assumed to biodegrade on both sides of the crack, (i.e., the original crack is bordered by biodegraded asphalt). These cracks in the upper corners are the first through-wall cracks in the asphalt barrier and they represent an avenue for water to enter and contaminants to leave the reinforced-concrete vault.

The appearance of through-wall cracks in the asphalt barrier, and the presence of the HDPE drainage net, geotextile, and thermal insulation board create a potential for biodegradation on the interior surface of the asphalt barrier. Infiltrating water could enter the engineered system and find its way to the interior surface, thus providing the necessary environment, (i.e., nutrients and microorganisms), for biodegradation to occur on both the interior and exterior surfaces of the asphalt barrier. Thus, interior and exterior surface biodegradation of the asphalt barrier is anticipated to begin during this time period.

The reinforced-concrete vault is assumed to experience three types of degradation during this time period; 1) increased cracking at roof-plank joints, 2) through-wall cracks at construction joints caused by corrosion of steel water stops, and 3) surface cracks on all concrete surfaces caused by rebar corrosion (see Figure O.8). The roof-plank joint cracks increase to 1-mm width. Construction joints are assumed to corrode and become 0.5-mm wide. There are a maximum of five (5) construction joints spaced vertically in each vault wall. These joints (steel water stops) are placed in the structure at the end of a concrete pour

S9211085 53

Figure O.8. Schematic Drawing Showing the Degradation During the 100 -10³ Year Period, and an Exploded View of Cracking on Concrete Surfaces

to ensure a good seal between one pour and the next. The contractor has the option to construct continuous walls that have no joints. The floor of the vault and the catch basin contain approximately 190 and 130 linear feet of construction joints respectively (see Figure 0.9). Surface cracking of reinforced-concrete is a result of the onset of rebar corrosion. This cracking does not result in through-wall cracks during this time interval; however, degradation of the surface does alter its hydraulic properties. For example, the porosity must increase when the concrete is cracked, the water retention relationships must also be different for intact and cracked concrete, and the saturated hydraulic conductivity must increase. These changes may cause the cracked concrete surface to be less conductive than the intact concrete in an unsaturated setting while being more conductive in a saturated setting. In addition, if saturated conditions result, the orientation of the surface dictates the flow direction because a preferential flow path is created. Wall surfaces become vertical flow paths, and floor surfaces become horizontal flow paths.

Following our conceptual model of the grout waste form and its degradation, seismic events and the transfer of external loads from the concrete vault structure to the grout monolith would cause fracturing of the grout monolith. Based on the spacing of corroded construction joints and the corresponding creation of 0.5-mm through-wall cracks at their locations in the concrete vault, when the grout monolith is exposed to seismic loads it is assumed the monolith will break into eight (8) blocks in the two-dimensional cross-section analyzed. It is further assumed that grout and concrete vault cracks would match up horizontally and vertically (i.e., align with the construction joints in the concrete vault).

During this period of time the grout, reinforced-concrete vault, gravel- catch basin, and asphalt barrier should come into hydraulic equilibrium with one another because of the cracks that have developed in the reinforced concrete structures and the hydraulic communication they allow. This equilibrium will depend both on the continuity of mass relationship and the constitutive equations adopted for the hydraulic characteristics of each engineered and natural component. Assuming grout is initially fully saturated, any liquid available for drainage from the grouted waste will drain through the corroded joints, along preferential flow paths associated with the drainage net and cracked concrete surfaces, into the gravel and catch basin, and finally into the unmaintained sump.

The current conceptualization of the disposal system focuses on liquid movement. However, a two-phase study of the vault and barriers is ongoing, and the presence of two (¼ inch o.d.) stainless steel gas vents (see Figure 0.10) connecting the gravel in the catch basin to the backfill soil plays an important role in any model including a gas phase. For the current study, i.e., this performance assessment, the gas vents are neglected as a pathway for liquids to migrate to the surrounding soil. Similarly, the steel riser extending from the sump, through the asphalt above the sump, and to the land surface is neglected as a long-term release pathway. It is believed that liquids under positive pressure (i.e., ponding in the catch basin) would drain through the degraded concrete structure and asphalt barrier before they would flood the catch basin and sump causing the gas vents and sump risers to release contaminated liquids.

(a) Construction joints in vault floor.

(b) Construction joints in catch basin and sump location.

S9211085.54

Figure O.9. Schematic Drawing Showing the Position of Construction Joints in the Vault Floor and the Catch Basin

O.5.3 Conceptual Model of the 10^3 - 10^4 Year Period

It is anticipated that degradation during this time period will involve continued biodegradation of the asphalt barrier (interior, exterior, and crack surfaces), a gradual increase in the size of existing concrete cracks, and the creation of patterned through-wall cracks in the reinforced-concrete as a result of rebar corrosion and seismic events (see Figure O.11). Again, note that the size and spacing of cracks described below are end-state descriptions, and should not necessarily be associated with the beginning of the time period.

Figure O.10: Schematic Drawing Showing the 1/4 Inch Gas Vents (0.25 inch O.D. and 0.18 inch I.D.) Placed in the Gravel Layer Between the Vault and Catch Basin

(a) End view cross-section of vault.

(b) Schematic of patterned cracks in reinforced concrete.

Figure O.11. Schematic Drawing Showing the Degradation During the 10^3 - 10^4 Year Period, and an Exploded View of Patterned Through-Wall Cracks in Reinforced Concrete

During this time period, the asphalt barrier continues to biodegrade. No new through-wall cracks develop. Biodegradation occurs on the interior and exterior surfaces of the barrier, and on crack surfaces associated with the horizontal and vertical cracks (5-mm) located in the upper corners of the barrier. These cracks and their neighboring biodegraded asphalt barrier (e.g., barrier aggregate) still represent the only through-wall openings in the asphalt barrier.

The reinforced-concrete vault is assumed to experience four types of degradation during this time period; 1) increased cracking at roof-plank joints, 2) increases in the size of through-wall cracks at construction joints caused by continuing steel water-stop corrosion, 3) increased cracking on all concrete surfaces because of rebar corrosion, and 4) creation of through-wall cracks resulting from rebar corrosion and seismic events. The roof-plank joint cracks increase to 2-mm width. The previously described wall and floor construction joints are assumed to further corrode and become 1-mm wide. Greater cracking of reinforced-concrete surfaces is a result of continued rebar corrosion. This corrosion and surface cracking has now weakened the structure to an extent that through-wall cracks develop (1-mm on 1-m grid) during this time interval. Continued degradation of concrete surfaces alters hydraulic properties even more. Creation of the more prevalent through-wall cracks associated with rebar corrosion and seismic stresses causes additional flow of fluid from the vault to the catch basin region. As in the previous time period, this flow follows the preferential flow paths, i.e., through-wall cracks in the concrete, drainage net, gravel-catch basin, and sump.

Following our conceptual model of grout degradation, seismic events and the transfer of external loads from the concrete vault structure to the grout monolith would cause additional fracturing of the grout monolith. Based on the through-wall crack spacing of the concrete vault, it is assumed the grout monolith will break into 1-m cubes. It is assumed that grout and concrete vault cracks will matchup horizontally and vertically.

During this period of time the grout, reinforced-concrete vault, gravel-catch basin, and asphalt barrier should continue to come into hydraulic equilibrium under the conditions of the additional cracks that have developed in the reinforced concrete structures and the hydraulic communication they allow. The only through-wall cracks in the asphalt barrier are still located at the upper corners. While some contamination will discharge from the upper corner of the disposal system, the movement of contaminant is largely within the engineered structure. Any liquid available for drainage from the grouted waste will drain through corroded joints and rebar corrosion cracks, along preferential flow paths associated with the drainage net and cracked concrete surfaces, into the gravel and catch basin, and finally into the unmaintained sump. As in the preceding time period, drainage from the catch basin and sump is assumed to be directed downward through the degraded structure and driven by any existing positive pressure caused by a buildup of liquid leached from the overlying structure. Thus, the presence of the gas vents and the sump riser is again neglected.

O.5.4 Conceptual Model of the 10^4 - 10^5 Year Period

It is anticipated that degradation during this time period will involve continuing interior and exterior surface biodegradation of the asphalt barrier, continued surface biodegradation in the 5-mm upper corner cracks, gradual increases in the size of existing surface cracks in concrete structures, an increase in the size and density of patterned through-wall cracks in the reinforced-concrete, an increase in the size and density of patterned cracks in the grout, and, finally, the appearance of patterned through-wall cracks in the asphalt barrier (see Figure O.12). The size and spacing of cracks described below are end-state descriptions, and should not necessarily be associated with the beginning of the time period.

The asphalt barrier is now degraded in two ways; 1) biodegradation of interior and exterior surfaces of the asphalt barrier and of all crack surfaces, and 2) patterned cracking on all asphalt barrier surfaces (top, bottom, and sides). The final state of patterned (1-mm on 1-m grid) through-wall cracks in the asphalt barrier is the result of embrittlement and recurring stresses related to seismic events. The patterned cracking also provides more surfaces for biodegradation. The two-surface biodegradation previously applied to cracks in the upper corners of the barrier is now also applied to the patterned through-wall cracks (see Figures O.12 and O.13). These patterned through-wall cracks and their biodegradation represent a significant flow path between the grouted waste and soil. The density of 1-m cracks is so great (see Figure O.12b) that it is highly improbable that all cracks would appear at the beginning of this time period. A more reasonable approach is to assume that cracks develop over some period of time. As an example, Figure O.13b shows the timing of the appearance of horizontal cracks in the walls of the asphalt barrier predicted by a linear model. In this particular model we assume the upper-corner cracks appear after 100 years, that thirteen (13) additional cracks appear in the ≈ 15 -m high wall, and that they appear linearly with respect to time over the $100 - 10^5$ year period. Suggested locations for cracks shown in the schematic columns superimposed on Figure O.13b are based on the assumptions that a crack will appear near the bottom early in the time period, and that the progression of crack generation follows a simple doubling pattern that further divides existing segments of the wall.

Figure O.12. Schematic Drawing Showing the Degradation During the 10^4 - 10^5 Year Period, and an Exploded View of Patterned Through-Wall Cracks in the Reinforced Concrete Vault and Asphalt Barrier

(a) Schematic showing sequence of biodegradation surfaces and of crack biodegradation and filling.

(b) End view of the sequence of horizontal cracks predicted with a linear pattern crack model.

Figure O.13. Schematic Drawings Showing a Cross-Sectional View of Biodegradation for an Intact and Cracked Asphalt Barrier, and a Semi-Log Plot of Crack Occurrence and Distribution as a Function of Time for Horizontal Wall Cracks from a Linear Cracking Model

The reinforced-concrete vault is assumed to experience four types of degradation during this time period; 1) maintenance of established cracks at roof-plank joints, 2) increased size of through-wall cracks at construction joints, 3) increased cracking on all concrete surfaces because of rebar corrosion, and 4) increased size and density of through-wall cracks resulting from rebar corrosion and seismic events. The roof-plank joint cracks remain at 2-mm width. The previously described wall and floor construction joints are assumed to further corrode and become 2-mm wide. Greater cracking of reinforced-concrete surfaces is a result of continued rebar corrosion. This corrosion and cracking has now further weakened the structure to the extent that additional through-wall cracks develop (2-mm cracks on 0.5-m grid) during this time interval.

Continued cracking of concrete surfaces alters hydraulic properties even more. Creation of the more prevalent through-wall cracks associated with rebar corrosion and seismic stresses causes additional flow of fluid from the vault to the catch basin region. As in the previous time period, this flow follows the preferential flow paths, i.e., through-wall cracks in the concrete, drainage net, gravel-catch basin, and sump. The release continues because of the drainage made possible by through-wall cracks in the asphalt barrier.

Seismic events and the transfer of external loads from the concrete vault structure to the grout monolith cause additional fracturing of the grout monolith. Based on the through-wall crack spacing of the concrete vault, it is assumed the grout monolith will break into 0.5-m cubes. It is again assumed that grout and concrete vault cracks matchup horizontally and vertically.

During this period of time the grout, reinforced-concrete vault, gravel-catch basin, and asphalt barrier will come into hydraulic equilibrium under the conditions of the additional cracks that have developed in the grout, reinforced concrete structures and the asphalt barrier. This implies a hydraulic equilibrium with the surrounding and underlying soil environment because of the hydraulic communication that cracks in the asphalt barrier allow. While some contaminant may still discharge from the upper corners, the dominant flow of water and transport of contaminant will be downward through the cracked and more conductive asphalt barrier. This conceptualization is based on the presence of the drainage net and cracked concrete surfaces. Under the unsaturated conditions anticipated, the hydraulic properties of these elements of the degraded engineered system should cause the greatest portion of the release to occur downward through the fractured concrete and cracked asphalt concrete underlying the vault. Lateral movement of water and waste across the fractured concrete surfaces and drainage net should be minimal provided unsaturated hydraulics govern the flow of water in the engineered system.

Consideration of the two stainless steel gas vents in the gravel layer separating the vault from catch basin, and of the carbon steel riser above the sump will no longer be necessary. It is assumed that discharge through the cracked asphalt barrier will dominate release from the engineered disposal system.

O.6 Initial Conditions

Initial conditions for the flow of water are outlined below for the various elements of the engineered disposal system, including the backfill soil, as shown in Figure O.2. Initial conditions for the transport of contaminant are concentration of zero ($c=0$) in all materials except the grout which is assigned unit concentration ($c=1$).

Backfill soil: initially assigned moisture content of 19%vol (10%wt) found to correspond with optimal compaction of backfill during placement around the present facility.

RCRA cover: initially assigned moisture content and related pressure shall be consistent with construction practice (considering optimal compaction and any constraints in placing high clay content materials).

Gravel: initially in equilibrium with the pressure in the backfill soil which surrounds gravel (this initial condition is assigned to both gravel deposits; the gravel wedge and gravel drain).

Asphalt barrier: initially dry (devoid of any water), contains maximum 4%vol voids, minimum 16.2%vol asphalt, and 79.8%vol aggregate. The assumption that the asphalt is initially dry is because the asphalt barrier is created and laid at high temperature. Thus, water is driven off prior to placement and compaction of the barrier.

HDPE drainage net: initially dry.

Steel-reinforced concrete: initially fully saturated and allowed to drain to reach an equilibrium with the HDPE drainage net.

Grout: initially fully saturated and allowed to drain to reach an equilibrium with the surrounding reinforced concrete vault.

Hanford formation: initially assigned moisture content consistent with the infiltration rate being simulated; 0.1 cm/yr for most cases.

Ringold formation: initially assigned moisture content consistent with the infiltration rate being simulated; 0.1 cm/yr for most cases.

O.7 Boundary Conditions

Boundary conditions for flow and transport simulations are outlined below for the upper, vertical, and lower boundaries.

O.7.1 Upper Boundary Underlying the Protective Barrier

Flow analysis: assign a uniform recharge of

- 0.1-cm/yr (expected short- and long-term boundary value)
- 5-cm/yr (unexpected greater recharge boundary value)

Transport analysis: create a zero convective and diffusive release boundary. Because the velocity is already assigned a downward directed value, one need not assign a Dirichlet or fixed concentration boundary condition to ensure a zero convective component to the release. Thus, one is able to assign a homogeneous Neumann boundary condition, (i.e., a fixed concentration gradient of zero). This will ensure zero convective and diffusive release at the upper boundary, but will allow the surface materials to be contaminated by upward diffusion if the diffusive process can overcome the convective process.

O.7.2 Vertical Symmetry Boundaries

Flow analysis: zero velocity normal to symmetry boundaries, ($v_n = 0$)

- left; symmetry with the adjacent vault under the same RCRA cover
- right; symmetry with the adjacent column of vault pairs

Transport analysis: zero concentration gradient normal to symmetry boundaries, ($\partial c / \partial n = 0$).

- left; symmetry with the adjacent vault under the same RCRA cover
- right; symmetry with the adjacent column of vault pairs

O.7.3 Lower Boundary at the Water Table

Flow analysis: the water table forms the bottom boundary of the domain

- pressure head (p) or matric potential (ψ) equals atmospheric pressure, ($p = 0$); or total head (p_t) equals elevation (z), ($p_t = z$).

Transport analysis: the bottom boundary is the interface between the unsaturated zone and the water table or unconfined aquifer. As such, contamination from the unsaturated zone should be able to enter the aquifer by both convective and diffusive processes, e.g.,

$$q_n = \alpha_{ni} q_i = \alpha_{ni} [v_i c - D_{ij} (\partial c / \partial x_j)]$$

However, some assumption would need to be made defining the relationship between the concentration and concentration gradient at the boundary. If this type of boundary condition is not available, the normal gradient should be assigned a zero value ($\partial c / \partial n = 0$). This will force all curie or mass flux to leave the domain through the convection process and enable one to readily calculate flux as a product of Darcy velocity and contaminant concentration.

O.8 Comments to be Resolved, July 9, 1993

When efforts to complete the best estimate conceptualizations, parameter estimations, and simulations were stopped in April 1993, this statement of the conceptual model was being reviewed by the Steering Committee. While time has permitted resolution of some of the comments received at that time, the following are unresolved comments.

Asphalt barrier: We should have some discussion of the impact of the actual base of vaults 102 through 105 on the overall performance of 33 vaults.

Seismic events: Some delineation should be made with regard to the approximate time scale implied by the use of long and short time periods with regard to seismic events. Perhaps some discussion of relative probabilities of a given seismic event could be used to make the distinction clear.

General description: A general description of the entire engineered system and the functions of the component parts would provide a good introduction to the sections discussing the degradation of the components. While Figure O.2 helps in this regard a summary paragraph of so would help with reader orientation.

Assumed: The word "assumed" is frequently used in the discussion. Where possible the discussion should be modified to indicate that some basis exists for making the particular assumption being discussed. This could be based on analysis or technical judgement or whatever. Failure to state the technical basis for an "assumption" will almost assuredly result in a technical challenge. The rewording of sentences incorporating the word "assumed" should be considered to make the presentation stronger.

Time line: A figure showing the time line of engineered structure degradation would be useful in keeping a reader on track and present the opportunity to present a comparison of the times that we are discussing in the PA, with historic events.

Temperature dependence of properties: In establishing the properties to be used in the analysis for the various components of the system, will influence of temperature on the effective diffusivity be

considered. Information published in 1981 suggest that elevated temperature (25°C compared to 90°C) can change the effective diffusivities of various constituents in a given waste form by three orders of magnitude.^(a)

A Thought Question: Given the discussion regarding the detection of leaks during the first 100 years and regarding the effectiveness of the asphalt liner, what should be our response be if we detect any fluid in the sump during the first 30 years? Would this indicate that the system had failed and that recovery was in order? What would be the effect of "early vault failure" on the dose to the public?

Seismic event analysis: The way the seismic events are discussed do not appear to be quite correct. As I understand the approach, the probability of a seismic event of a given magnitude increases with time. As such for a particular structure with a life time of 30 years, there is a probability X of experiencing a seismic event of magnitude M. As the life of the structure is increased, the probability of experiencing a seismic event of a given magnitude M increases (becomes greater than X). Summarily, for a given probability of occurrence X the magnitude of the event that the longer lived structure will sustain will increase (becomes greater than M). But, the absolute timing of the event is largely unknown. As such it is difficult to say with any assurance that a seismic event of a given magnitude will occur in any given time period.

Design basis events: One possible strategy that could be used to develop a basis for degradation and degraded system response would be to develop a series of "design basis events" that the engineered disposal system would be subjected to at on a predetermined schedule. The disposal system in its degraded state could be subjected to seismic events to help quantify the integrity of the system over the long term. Such a series of design basis events could be shown to be conservative based on statistical analysis of the historic and archaeological record.

Simplify the writing to assure readability: I (R. Karnesky) found (the description of the best estimate conceptual model) to be reasonably complete and to have a good fundamental basis (when taken together with the earlier information presented to the Steering Committee). Realizing that the prediction of the degradation of engineered barriers and engineered systems is highly uncertain, I felt that it was a credible job. The writing, while clear was, in my opinion unnecessarily complex and needs to be simplified in the final document to assure readability.

Study of pore-volumes of infiltration contacting waste: The amount of contact between grouted waste and infiltrating water could be further explored and quantified through simulations by labeling the infiltrating water, (not the waste in the grout), and tracing the infiltration front.

(a) Barnes, M. W., et al. 1981. "Stability of I and Sr Radiophases in Cement Matrices." *Scientific Basis for Waste Management* Vol. 6, pp. 147-154.

Hydraulics and contaminant release: Prior to simulating "degraded" grout, some comparative modeling should be performed to determine the implications for contaminant release from different conceptualizations of fractured grout and from assumed hydraulics characteristics of mineral deposits in cracks.

Backfill soil geochemistry: It would be useful if a discussion regarding the types of rocks and minerals found in the back-fill soil and/or the gravel was included to provide a basis and justification for the assumed formation of calcium carbonate as infiltration contacts the cementitious vault and waste.

Unconfined aquifer: A description of the aquifer initial and boundary conditions should be provided; any changes in climate over time that would lead to changes in water table elevation should be described or the possibility discussed.

Volume stability: Note the solid nature of the waste and engineered structure result in negligible potential for loss of volume and settlement.

Figures of I.C. and B.C.: Prepare and include graphic depictions of initial and boundary conditions for both the unsaturated zone and the unconfined aquifer.

Parameter assignments: Alternate approaches need to be presented for arriving at the most likely case(s); approaches to modeling the features in the conceptual model; approaches to making parameter assignments consistent with conceptual model and all field and laboratory data.

Degradation of grout: The document needs a consistent logic for grout degradation: consistent with mechanisms identified for concrete and asphalt, and consistent with the knowledge of grout from other DOE sites, e.g., Savannah River.

Corrosion of reinforcing steel: The vault contains cross tie stirrups (No. 5, 5/8 inch diameter rebar) and it is not clear that corrosion of these stirrups has been considered in crack development estimates.

Natural analogues: Stronger comparisons need to be made between analogues such as Portland and ancient cements, and the AR-6000 asphalt and natural asphalt.

During the initial 100 to 300 years when temperature cycles occur, (e.g., (1) asphalt pour, compaction and cooling, (2) 90°C grout cure period, and (3) 55°C cesium decay period could cracking of the asphalt occur during cooling?

Gravel: There is a need to study several aspects of the integrity of the gravel wedge. How large a depression or soil infiltration zone can the gravel tolerate before downward drainage would result?

Hydraulic and transport properties: There is a need to measure and use hydraulic and transport properties of intact and degraded components of the system, (i.e., asphalt barrier, steel-reinforced concrete, grout, gravel, etc).

Degradation: There is need to quantify the degradation possible at key points, (e.g., construction joints, roof-plank joints, HDPE flow net, gravel).

O.9 References

58 FR 7924. 1992. U.S. Environmental Protection Agency. "Environmental Radiation Protection Standards for the Management and Disposal of Spent Nuclear Fuel, High-Level and Transuranic Radioactive Wastes." Proposed Amendment to 40 CFR 191. *Federal Register*.

10 CFR Part 61. U.S. Nuclear Regulatory Commission. "Licensing Requirements for Land Disposal of Radioactive Waste." *U.S. Code of Federal Regulations*.

Dames and Moore. 1989. "Report of Geotechnical Investigation, Proposed Hanford Waste Vitrification Plant; Hanford, Washington." Prepared for Kaiser Engineers Hanford Company, November 15, 1989. Dames and Moore, Richland, Washington.

Fayer, M. J., and M. R. Rockhold. 1993. *Physical and Hydraulic Properties of Sediments and Engineered Materials Associated with Grouted Double-Shell Tank Waste Disposal at Hanford*. PNL-xxxx, Pacific Northwest Laboratory, Richland, Washington.

Gee, G. W., M. J. Fayer, M. L. Rockhold, and M. D. Campbell. 1992. "Variations in Recharge at the Hanford Site." *Northwest Science* 66(4):237-250.

Gruhlke J. M., F. L. Galpin, and W. F. Holcomb. 1989. "Overview of EPA's Environmental Standards for the Land Disposal of LLW and NARM Waste--1989." In *Eleventh Annual Department of Energy Low-Level Waste Management Conference*, Vol. 1, RU24-RU32. CONF-890854. Idaho National Engineering Laboratory, Idaho Falls, Idaho.

Jury, W. A., W. R. Gardner, and W. H. Gardner. 1991. *Soil Physics (fifth edition)*. John Wiley & Sons, New York.

Kaiser Engineers Hanford Company. 1989. "Construction Specifications for the Diffusion Break (for grouted waste disposal facilities, grout vault pair 218-E-16)." Specification #B-714-C2, Rev 1, Section 02147, pages 02147-1 - 02147-10.

Lindberg, J. W., J. V. Borghese, B. N. Bjornstad, and M. P. Connelly. 1992. *Geology and Aquifer Characteristics of the Grout Treatment Facility*. WHC-SD-EN-TI-071, Rev. 0, Westinghouse Hanford Company, Richland, Washington.

Luey, J., and S. W. Li. 1993. *Determination of the Biodegradation Rate of Asphalt for the Hanford Grout Vaults*. PNL-8599, Pacific Northwest Laboratory, Richland, Washington.

U.S. Department of Energy (DOE). 1987. *Final Environmental Impact Statement: Disposal of Hanford Defense High Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington*. Volume 1 and Volume 3, Appendices O, P and Q. DOE/EIS-0113, Vol 1-5, U.S. Department of Energy, Washington, D.C.

U.S. DOE. 1988a. "Radioactive Waste Management." DOE Order 5820.2A.

U.S. DOE. 1988b. *Internal Dose Conversion Factors for Calculation of Dose to the Public*. DOE/EH-0071. U.S. Department of Energy, Washington, D.C.

U.S. DOE. 1990. "Radioactive Waste Management." Richland Operations Supplement to DOE Order 5820.2A.

Appendix P

Additional Details of Data, Analysis, and Results

Appendix P

Additional Details of Data, Analysis, and Results

The arrangement of this appendix follows the organization of Chapters 3 and 4 of the performance assessment. The section headings in this appendix identify the corresponding text material from the performance assessment chapters. This appendix is intended to complement the information in the performance assessment and is not written as a "standalone" document. Additional detail is provided only for select sections of the performance assessment; thus, if additional information was available to support Sections 4.1 and 4.3, but not Section 4.2, only Sections 4.1 and 4.3 would be represented here.

P.1 Section 3.2.5, Flow and Transport Models

The stated purpose of the companion text in the performance assessment was to define terminology, but to do so without relying on or providing detailed equations. In this section a similar presentation is presented; however, equations are employed to more clearly illustrate the relationships between predicted quantities and model parameters. Most material will follow the sequence of topics that appeared in Section 3.2.5 of the performance assessment. However, material is appended to the section on water flow on the following special topics: 1) methods for calculating equivalent saturated hydraulic conductivity and 2) a composite hydraulic model for unsaturated flow in cracked or fractured media. Material on the special transport topic of methods for calculating equivalent diffusion coefficients follows the Section 3.2.5.2 on contaminant transport.

P.1.1 Section 3.2.5.1, Water Flow

Brief descriptions of the equations governing water flow in saturated and unsaturated porous media are followed by a similarly brief presentation of equations governing water vapor diffusion.

Saturated Water Flow. Water flowing through a porous media is governed by the empirical relationship known as Darcy's law and the equation describing the conservation of water mass (Freeze and Cherry 1979). Written in a one-dimensional form, Darcy's law is:

$$Q = -K \frac{dh}{dl} A \quad (P.1)$$

where Q = flow rate (L^3/T)

K = hydraulic conductivity (L/T)

dh/dl = hydraulic gradient (L/L)

h = hydraulic head (L)

l = length or longitudinal spatial coordinate (L)

A = cross sectional area (L^2).

In Equation P.1, the flow rate is proportional to the hydraulic conductivity multiplied by the hydraulic gradient (change in hydraulic head, h , in the direction of flow, l) and the cross sectional area. The proportionality constant for this empirical relationship is contained within the hydraulic conductivity. The average linear velocity of water (v) is the flow rate divided by the cross sectional area of the water. This cross section is the total cross section (A) multiplied by the effective porosity in the case of ground-water flow or by water content in the case of unsaturated flow. In equation form, the average linear velocity is as follows:

$$v = Q/(An_e) \text{ for saturated media} \quad (P.2)$$

or

$$v = Q/(A\theta) \text{ for unsaturated media} \quad (P.3)$$

where v = average linear velocity, or pore-water velocity (L/T)

n_e = effective porosity of a saturated porous medium (-)

θ = volumetric moisture content in an unsaturated medium (-)

and Q and A are as defined above.

Water movement through saturated porous media is governed by the combination of Darcy's law and the conservation of water mass. The latter is quantified through a simple control volume approach where the water mass entering and leaving is equated to the change in water mass within the control volume. Darcy's law is used to relate hydraulic gradient to the rate at which water enters and leaves the

control volume. Changes in the ability of a porous medium to store water are also related to the hydraulic head. The resulting basic equation used to describe transient water flow in a saturated porous media is expressed as follows (Freeze and Cherry 1979):

$$\frac{\partial}{\partial x} \left(K_x \frac{\partial h}{\partial x} \right) + \frac{\partial}{\partial y} \left(K_y \frac{\partial h}{\partial y} \right) + \frac{\partial}{\partial z} \left(K_z \frac{\partial h}{\partial z} \right) = S_s \frac{\partial h}{\partial t} \quad (\text{P.4})$$

where K_x , K_y and K_z are saturated hydraulic conductivities in the x, y and z directions (L/T), h is hydraulic head (L), and S_s is specific storage (L^{-1}).

Solution of this equation and its associated initial and boundary conditions provides the spatial distribution of hydraulic head, $h(x,y,z,t)$, at points in space and moments in time. Simulations based on the above, or similar forms of the groundwater flow equation, also depend on a knowledge of the spatial distributions of basic geohydrologic parameters of hydraulic conductivity and specific storage, and the fundamental geometry of the flow system such as the thickness and areal extent of the flow system or aquifer.

Definitions of Potential and Pressure Head. Water movement within the unsaturated zone is governed by the total water potential, ψ_t , which is the combination of the soil water potential, ψ_w , and the gravitational potential, ψ_z , i.e.,

$$\psi_t = \psi_w + \psi_z \quad (\text{P.5})$$

Water potential is formally defined (Hanks and Ashcroft 1980, pg 20-28) as the amount of work that a unit quantity of water in an equilibrium soil-water system is capable of doing when it moves to a pool of water in the reference state at the same temperature. The reference state commonly chosen is pure free water at a specific elevation and temperature.

The soil water potential, ψ_w , is more easily understood if it is broken down into component potentials; pressure, solute, and matric potentials, e.g.,

$$\psi_w = \psi_p + \psi_s + \psi_m \quad (\text{P.6})$$

All of the potentials are defined with regard to a unit quantity of water. However, three methods of specifying the unit quantity exist; mass, volume, and weight. If the quantity of water is expressed as a weight, the units of potential in the SI system are centimeters (cm) of water. If the quantity of water is expressed as a volume, the units of potential are dynes/cm² (the same units as pressure).

Weight is one of the most convenient methods of specifying the unit of water potential. Gravitational potential, ψ_z , is then the difference in elevation of the point in question and a reference point.

The matric potential, ψ_m , is related to the adsorptive forces of the soil matrix (hence the term "matric"). If the quantity of water is expressed as a weight, matric potential is the vertical distance between that point in the soil and the water surface of a manometer filled with water and connected to the soil point in question via a ceramic cup. In an unsaturated soil the water surface of the manometer will always be below the point in the soil, and the matric potential is a negative quantity. In a saturated soil (e.g., at and below the water table) the matric potential is generally assigned a value of zero.

The pressure potential, ψ_p , applies to saturated soils. Where water is expressed as a weight, pressure potential is the vertical distance from the point in question in the soil to the water surface of a piezometer connected to the point. Pressure potential is zero at and above the level of the water in the piezometer. Below this level, pressure potential is always positive and it increases with increasing depth below this water level.

Solute potential, ψ_s , arises because of soluble materials, such as salts, in the soil solution and the presence of a semipermeable membrane in the system (Hanks and Ashcroft 1980, pg 50-51). A semipermeable membrane is a material that allows water to flow but does not permit salts to pass through it. In soils alone, the solute potential is relatively unimportant in liquid water flow because there are no semipermeable membranes. However, cell walls in plant roots do represent non-perfect membranes, and air-water interfaces are near perfect membranes. In soil physics one is often interested in the salt concentration that produces a given solute potential. An approximate relationship is given by

$$\psi_s = - RTC_s \quad (P.7)$$

where R is the universal gas constant (82 bars cm³/mol K), T is absolute temperature (K), and C_s is solute concentration (mol/cm³). However, an exact value of C_s is difficult to estimate because it is the summation of all species including the dissociation into ionic species in the soil water.

In general, one is concerned only with liquid water flow in the soil, and the solute component is assumed to be essentially zero. For liquid water flow in the absence of a solute potential component, the total potential is,

$$\psi_t = \psi_p + \psi_m + \psi_z \quad (\text{P.8})$$

This combination of potentials appears often in analyses of soil water, and therefore, it has been given the name hydraulic potential, ψ_h , (i.e., $\psi_t = \psi_h$ when $\psi_s = 0$).

Often, in unified models of liquid water flow in porous media, (i.e., those that address water flow in both unsaturated and saturated domains), the general term used to describe the dependent variable is not soil water potential, ψ_w , but "pressure head, h." This terminology evolved from the modeling of saturated ground water systems which predates the simulation of unsaturated domains, and the use of length (cm) units to quantify both pressure head in the saturated system and potential in the unsaturated system. Within the numerical model the dependent variable, pressure, is negative in the unsaturated domain, zero at the water table of the unconfined aquifer, and positive in the saturated domain beneath the water table.

Unsaturated Water Flow. In the saturated zone all pores are filled with water, in the unsaturated zone they are not. A positive water pressure exists in the saturated zone while a negative pressure exists in the unsaturated zone. Darcy's law and the conservation of water mass still govern the movement of water; however, Darcy's law must be modified to account for capillary forces which affect both the driving force (pressure) and the hydraulic conductivity in the unsaturated zone. These modifications to Darcy's law were first recognized by Buckingham in 1907 (Jury et al. 1991) and were incorporated into the governing equation for transient water flow in the unsaturated zone by Richards (1931). Hence, the classical equation used to describe transient unsaturated water flow is known as Richards' equation, i.e.,

$$\frac{\partial}{\partial x} \left[K_x(\psi) \frac{\partial \psi}{\partial x} \right] + \frac{\partial}{\partial y} \left[K_y(\psi) \frac{\partial \psi}{\partial y} \right] + \frac{\partial}{\partial z} \left[K_z(\psi) \left(\frac{\partial \psi}{\partial z} + 1 \right) \right] = C(\psi) \frac{\partial \psi}{\partial t} \quad (\text{P.9})$$

where $K_x(\psi)$, $K_y(\psi)$, $K_z(\psi)$ = unsaturated hydraulic conductivities (L/T) in the x, y and z directions which are a function of pressure head or tension (L/T)

ψ = pressure head or tension (L) which is dependent on the degree of saturation, S, or moisture content, θ

C = specific capacitance (L^{-1}) and is defined as $d\theta/d\psi$

S = saturation is θ/n , where θ is the moisture content (dimensionless) and n is the porosity of the media (dimensionless).

The solution of Richards' equation with associated initial and boundary conditions defines the pressure head, $\psi(x,y,z,t)$, in an unsaturated domain at points in space and moments in time. Pressure head is

converted to total hydraulic head, $h(x,y,z,t)$, by adding the elevation head (z = vertical distance from an arbitrarily assigned elevation datum) to the pressure head, i.e., $h = \psi + z$. It is the gradient of total head that determines the movement of water in the unsaturated zone. In addition to a knowledge of initial and boundary conditions, and the geometric constraints of the system (e.g., the thickness and areal extent of soil layers), simulation of the unsaturated zone requires a knowledge of soil characteristic relationships for each soil strata or layer modeled. These relationships define moisture content as a function of pressure head, and unsaturated hydraulic conductivity or relative permeability as a function of pressure head, i.e.,

$$\theta = \theta(\psi) \quad (P.10)$$

$$K = K(\psi), \text{ or } K = K_{\text{sat}}K_r(\psi) \quad (P.11)$$

where $K(\psi)$ = unsaturated hydraulic conductivity (L/T)

K_{sat} = saturated hydraulic conductivity (L/T)

$K_r(\psi)$ = relative hydraulic conductivity, K/K_{sat} (-).

Classical examples of characteristic curves illustrating the influence of soil texture on water retention and unsaturated hydraulic conductivity are shown in Figures P.1 and P.2.

Use of the characteristic curves in numerical models generally requires that the data be described by analytical models. This technique promotes efficiency in numerical solutions because values can be determined exactly, thus avoiding interpolation between data points in a table and assuring continuous derivatives necessary for evaluating the specific capacitance. A number of methods have been developed to describe characteristic curves. The relationship selected for use in this performance assessment is a closed-form analytical model for representing the water retention characteristics and unsaturated hydraulic conductivity function, published by van Genuchten (1978).

From the van Genuchten method, the moisture content (θ) as a function of pressure head (ψ) is given by:

$$\theta = (\theta_s - \theta_r) \left[\frac{1}{1 + (\alpha\psi)^n} \right]^m + \theta_r \quad (P.12)$$

S9211085.48

Figure P.1. Example of Water Retention Characteristics Showing the Effect of Soils with Different Textures (Hillel 1982, p. 76)

S9211085.47

Figure P.2. Example of Unsaturated Hydraulic Conductivity Showing Its Dependency on Pressure in Soils of Different Textures (log-log scale) (Hillel 1982, p. 113)

where $m = (1 - 1/n)$

θ = the volumetric moisture content

θ_s = saturated volumetric water content (dimensionless)

θ_r = residual volumetric water content (dimensionless)

α = fitting parameter (L^{-1}), approximately equal to the air entry pressure

n = fitting parameter (dimensionless)

ψ = the pressure head or capillary pressure head.

The saturated and residual moisture contents, and fitted parameters α and n , are parameters for which specific values are provided from measured data for each of the specific materials or soils involved in the problem set (see Appendix J).

From this relationship, the hydraulic conductivity can be expressed in terms of a pressure relationship as a function of the moisture content. One method developed by Mualem (1976) was used in the performance assessment to estimate unsaturated hydraulic conductivity from the water-retention data. Mualem's model is based on the relationship between the pore size distribution and water retention characteristics and is expressed by the following equation:

$$K_r(S_e) = S_e^n \left[\int_0^{S_e} \frac{dS_e}{h} / \int_0^1 \frac{dS_e}{h} \right]^2 \quad (P.13)$$

where K_r = relative hydraulic conductivity (dimensionless)

S_e = effective saturation (dimensionless).

Based on the best fit of this model to 45 soils, Mualem (1976) indicated that the exponent n should be 0.5.

Van Genuchten (1978) used the water retention function given in Equation P.8 and solved Equation P.9 analytically. This solution is given in the following expression:

$$K_r = \frac{K}{K_s} = \frac{\{1 - (\alpha\psi)^{n-1}[(1 + (\alpha\psi)^n]^{-m}\}^2}{[1 + (\alpha\psi)^n]^{m/2}} \quad (P.14)$$

where $m = (1 - 1/n)$

K_r = the relative hydraulic conductivity (dimensionless)

ψ = the capillary pressure head in centimeters of water

K_s = the saturated hydraulic conductivity in cm/s

and α , n are the fitted parameters. This equation can be used to develop the relationship of pressure head to unsaturated hydraulic conductivity as depicted in Figure P.2. Parameters specific to the materials included in this performance assessment and based on available data are presented in Appendix J.

Water Vapor Flow. Water vapor diffusion (or return) will not lead to significant releases of radionuclides while the asphalt barrier remains intact. However, the source of water becomes more significant if the asphalt barrier degrades and cracks over time. The relative importance of water vapor diffusion is increased if advection through the grout is limited (e.g., by the capillary break provided by the gravel layer currently planned to be placed over the grout vaults). The rate of water vapor diffusion or return to the grout or concrete surface can be calculated using the following expression of the diffusion equation:

$$m = -D_v \frac{dC}{dx} A \quad (P.15)$$

where m = mass rate of water diffusion to the grout or vault surface (M/T)

A = effective diffusional cross sectional area of the vault (L^2)

D_v = vapor diffusivity (L^2/T)

dC/dx = gradient of the vapor concentration (M/L^3)

x = thickness of the barrier material (L)

and the change in concentration is calculated using a knowledge of the depression in vapor pressure and the ideal gas assumption.

Equivalent Saturated Hydraulic Conductivity. Of the five parameters in the van Genuchten-Mualem model which define unsaturated soil hydraulic characteristics (θ_s , θ_r , α , n , and K_{sat}), only the

saturated hydraulic conductivity, K_{sat} , can be defined in an equivalent sense based on available literature. This equivalence can be done rigorously only for saturated applications to fluid flow in porous media. The application in this performance assessment is to unsaturated fluid flow. Therefore, the unsaturated hydraulic conductivities produced by the van Genuchten-Mualem model using the equivalent K_{sat} were assumed to be appropriately scaled by the relative permeability function. There are actually two classical equivalent models defined in the literature (Harr 1962, pg. 27)—one for flow parallel to the strata having different values of saturated hydraulic conductivity, and another for flow perpendicular to the strata.

Assuming fluid flow parallels the stratification (e.g., flow is horizontal in a horizontal crack and in the media surrounding the crack, or flow is vertical in a vertical crack and in the media surrounding the crack), the cumulative discharge from the different strata must be duplicated by an equivalent hydraulic conductivity, K_{sat}^{eq} . Flow in each strata is driven by the same hydraulic gradient and it also applies to the equivalent porous media. Thus, as shown by Harr (1962, pg. 27) the equivalent saturated hydraulic conductivity in the direction of flow will be:

$$K_{sat}^{eq} = \sum_{m=1}^n \left[K_{sat}^m \cdot d_m \right] / d_{total} \quad (P.16)$$

where K_{sat}^{eq} = equivalent saturated hydraulic conductivity (L/T)

K_{sat}^m = saturated hydraulic conductivity of the m^{th} strata or layer (L/T)

d_m = thickness of the m^{th} strata or layer (L)

d_{total} = total thickness of the computational cell (L)

n = number of strata or layers in the computational cell.

The equivalent saturated hydraulic conductivity that applies to a computational cell for a porous media equivalent to a partially biodegraded asphalt is based on the theory of equivalent properties for flow perpendicular to the direction of stratification (Harr 1962, pg. 27). Assuming water flow is unidirectional and perpendicular to the stratification (e.g., flow is horizontal through a series of vertically aligned strata, or vertical through a series of horizontal strata), the flow defined by Darcy's equation through each of the different strata must be equal. However, Darcian flow through each will be driven by a different hydraulic gradient. This same Darcian flow can be duplicated by an equivalent saturated hydraulic conductivity, K_{sat}^{eq} , which uses the overall or cumulative hydraulic gradient across all the strata. As shown by Harr (1962, pg. 27), the equivalent saturated hydraulic conductivity will be:

$$K_{sat}^{eq} = d_{total} \left\{ \sum_{m=1}^n \left[d_m / K_{sat} \right] \right\}^{-1} \quad (P.17)$$

where the definition of variables are unchanged from the preceding equation.

Composite Hydraulic Model for Cracks. An alternate conceptual model for incorporating the hydraulic influence of through-wall cracks consists of a composite model in which the crack properties (assumed to be those of backfill soil) are combined with concrete matrix properties to form the composite material's (both cracks and matrix) properties. The composite model (Klavetter and Peters 1986) was selected because it is based on the assumption that pressure head is the same in both the matrix and fracture. For a given pressure head, the saturations for the fractures (S_f) and for the matrix (S_m) are calculated using the van Genuchten moisture retention curves with backfill soil parameters for S_f and concrete parameters for S_m . The composite material saturation (S_c) is calculated by the following equation:

$$S_c = [S_f \cdot ECF + S_m \cdot (1 - ECF) \cdot 0.2258] / n_e \quad (P.18)$$

where ECF = effective crack fraction (dimensionless)

0.2258 = porosity of concrete matrix (dimensionless)

n_e = effective porosity of composite material $[ECF + (1 - ECF) (0.2258)]$ (dimensionless).

The relative permeability ($k_{r,c}$) of the composite material is given by the following equation:

$$k_{r,c}(S_c) = [K_f \cdot ECF \cdot k_{r,f}(S_f) + K_m \cdot (1 - ECF) \cdot k_{r,m}(S_m)] / K_{sat} \quad (P.19)$$

where ECF = effective crack fraction (dimensionless)

K_f = fracture saturated conductivity = 3×10^{-2} cm/s

$k_{r,f}$ = relative permeability of crack = relative permeability of backfill soil as a function of S_f (Mualem model is used) (dimensionless)

K_m = matrix saturated conductivity = 3.75×10^{-10} cm/s

$k_{r,m}$ = relative permeability of matrix (concrete properties) as a function of S_m (dimensionless)

$$K_{sat} = \text{composite material saturated conductivity } [K_f(\text{ECF}) + K_m(1 - \text{ECF})] \text{ (L/T)}.$$

P.1.2 Section 3.2.5.2, Contaminant Transport

Terms are defined and equations presented for transport phenomena in porous media as modeled in this performance assessment. Additional details are provided for the topics of diffusion and sorption which appear in the body of the report. In addition, concepts used to determine equivalent diffusion coefficients for diffusion parallel and perpendicular to sediment stratification are given.

Diffusion. Diffusion may be driven by a combination of different forces which may or may not act in a particular situation. In pressure diffusion, the presence of a significant pressure gradient may cause some separation of a mixture. In forced diffusion, separation of a mixture may result if there is an external force acting unequally on different components of a mixture. An example of such a system would be an ionic solution with differently charged ions under the influence of an electrical field. Thermal diffusion occurs in systems in which there is a strong thermal gradient present. However, in the vast majority of applications the most important type of diffusion is that which occurs in response to a concentration gradient. A more complete discussion of diffusion effects is provided by Bird, Stewart, and Lightfoot (1960, pg. 567). In this performance assessment, only ordinary diffusion which is driven by a concentration gradient is considered. The mass of a diffusing contaminant through a given cross sectional area per unit time is proportional to the negative of the concentration gradient. This relationship, Fick's first law, can be written as (Freeze and Cherry 1979, page 103):

$$F = -D \frac{dC}{dl} A \quad (\text{P.20})$$

where F = mass flux per unit time (M/T)

D = diffusion coefficient in the conducting fluid (L^2/T)

C = solute concentration (M/L^3)

dC/dl = concentration gradient (M/L^4), a negative quantity in the direction of diffusion.

The transport of contaminants from the vault and through the engineered system and natural environment has been modeled using the advection-diffusion equation. Sorption was also considered, but it will be added to the equation later. If the transport were purely diffusive, Fick's first law would be

combined with the equation of continuity for diffusive flux. The differential equation known as Fick's second law is obtained, which relates the concentration of the diffusing substance in space and time (Freeze and Cherry 1979, page 104), i.e.,

$$\frac{\partial C}{\partial t} = D^* \frac{\partial^2 C}{\partial x^2} \quad (P.21)$$

where D^* is the apparent diffusion coefficient for mobile chemical species in the porous media. Apparent diffusion coefficients for ions in porous media are smaller than in water because ions in the fluid follow longer, more tortuous paths as a result of the solid matrix. The apparent coefficient value, D^* , is related to the diffusion coefficient in water

$$D^* = \omega D \quad (P.22)$$

where ω is always less than one and accounts for the tortuosity of the pores. Laboratory values of ω range from 0.5 to 0.01 (Freeze and Cherry 1979, page 104).

The governing equation for advective and diffusive transport can be derived using the control volume concept and accounting for both advective and diffusive flux. The resulting equation of continuity, combined with Fick's first law and the Buckingham modified Darcy's law, yields the following governing equation:

$$D^* \left(\frac{\partial^2 C}{\partial x^2} + \frac{\partial^2 C}{\partial y^2} + \frac{\partial^2 C}{\partial z^2} \right) - v_x \frac{\partial C}{\partial x} - v_y \frac{\partial C}{\partial y} - v_z \frac{\partial C}{\partial z} = \frac{\partial C}{\partial t} \quad (P.23)$$

where v_i = average linear velocity (L/T) in the i^{th} direction, ($i=1,2,3 \Rightarrow x,y,z$)

D^* = apparent diffusion coefficient (L^2/T)

C = solute concentration in the aqueous phase (M/L^3).

This form of the equation is written for non-reactive, dilute, dissolved constituents in homogeneous, isotropic flow systems under both steady-state and unsteady flow field conditions. Solution to Equation P.23 provides the distribution of solute concentrations at points in space and moments in time. This

solution requires knowledge of the average linear velocity along the flow path and the apparent diffusion coefficient. If the tortuosity correction is neglected, the diffusion coefficient must be known.

Water content is known to affect diffusion, and hence the effective diffusion coefficient, in unsaturated soils (Kemper and van Schaik 1966). The molecular diffusion coefficient for all species in pore water was assumed to be $2.5 \times 10^{-5} \text{ cm}^2/\text{s}$. In this analysis, the effective diffusion coefficients for the RCRA cover, backfill soil, and underlying natural sediments of the unsaturated profile were modified according to the empirical relationship published by Kemper and van Schaik (1966). The effective diffusion coefficient as a function of the volumetric moisture content is as follows:

$$D_e(\theta) = D_{ab} (a) (e^{b\theta}) \quad (\text{P.24})$$

where D_e = effective diffusion coefficient of an ionic species in a particular soil

D_{ab} = effective diffusion coefficient of the same species in water.

Data collected by Olsen, Kemper and van Schaik (1965) and Porter et al. (1960) for soils using sodium chloride as the diffusing species fit the equation with " $b = 10$ " and " a " being a function of soil surface area. The soils used in these studies ranged from sandy loam to clay soils, with the value for " a " ranging from 0.005 to 0.001, respectively (Olsen and Kemper 1968).

To be consistent with the measured data, values of " a " and " b " were selected as 0.005 and 10, respectively, for this performance assessment. These coefficients were measured for several Hanford soils using NaNO_3 in a half-cell diffusion experiment. The coefficients determined in the experiments gave comparable estimates of the effective diffusion coefficients in the soil at expected water contents.

Equivalent Diffusion Coefficients. As in the case of hydraulic properties, there are two classical equivalent diffusion coefficient models that have been defined in the literature (Crank 1975) and are applicable to this study--one for diffusion parallel to a suite of strata having different diffusion coefficient values, and another for diffusion orthogonal to the strata.

The equivalent diffusion coefficient that applies to a computational cell for a porous media equivalent to a partially biodegraded asphalt is based on the theory of equivalent properties of laminates under steady-state conditions (Crank 1975, pg. 267). Assuming diffusive transport is unidirectional and orthogonal to the stratification (e.g., diffusion is horizontal through a series of vertically aligned strata, or vertical through a series of horizontal strata), the transport by diffusion through each of the different strata must be equal. However, diffusive transport through each will be driven by a different concentration

gradient. This same diffusive transport can be duplicated by an equivalent diffusion coefficient, D_{eq} , which uses the overall or cumulative concentration gradient across all the strata. As shown by Crank (1975, pg. 267), the equivalent diffusion coefficient will be:

$$D_{eq} = d_{total} \left\{ \sum_{m=1}^n \left[d_m / D_m \right] \right\}^{-1} \quad (P.25)$$

where D_{eq} = equivalent diffusion coefficient (L^2/T)

D_m = diffusion coefficient of m^{th} strata or layer (L^2/T)

d_m = thickness of the m^{th} strata or layer (L)

d_{total} = total thickness of the computational cell (L)

n = number of strata or layers in the computational cell.

Equivalent diffusion coefficients for computational cells containing a crack are based on a similar concept. Assuming diffusive transport is unidirectional and parallel to the stratification (e.g., diffusion is horizontal in a horizontal crack and in the surrounding media, or vertical in a vertical crack and in the surrounding media), the cumulative transport by diffusion from the different strata must be duplicated by an equivalent diffusion coefficient, D_{eq} . The same concentration gradient applies to the individual strata and the equivalent media. Thus, as shown by Crank (1975, pg. 273), the equivalent diffusion coefficient in the direction of flow will be:

$$D_{eq} = \sum_{m=1}^n \left[D_m \cdot d_m \right] / d_{total} \quad (P.26)$$

where the definition of variables is unchanged from the preceding equation. As in the preceding case, and to be consistent with the hydraulic properties assigned to cracks in the engineered structure, the diffusion coefficient of the backfill soil is assigned to the crack.

Dispersion. No additional information or equation development included because the dispersion process was not explicitly modeled.

Sorption. The transport of some contaminants from the grout waste through the barrier system into the vadose zone and into the underlying groundwater system will also be affected by the geochemical interaction of the contaminants with surrounding solids and liquids. The net effect of geochemical interactions is quantified by the linear sorption isotherm model and ultimately by an empirical parameter referred to as the distribution coefficient (R_d). The distribution coefficient is a term used to represent all contaminant sorption or retardation processes such as chemical precipitation/dissolution, adsorption/desorption, filtration of colloids, cation-anion exchange, and exchange of stable isotopes with a radionuclide. R_d is determined in the laboratory on soil samples or estimated from groundwater concentrations. This coefficient is the ratio of the amount of sorbed species per gram of solid to the amount of the species remaining in solution per milliliter. The relationship between the R_d for porous media and the retardation factor which appears in the transport equation is commonly expressed in the following manner (Freeze and Cherry 1979):

$$R = 1 + (\rho_b/\theta)R_d \quad (P.27)$$

where R = retardation factor (dimensionless)

ρ_b = bulk density of the material (M/L^3)

θ = volumetric water content of the material (dimensionless)

R_d = distribution coefficient (L^3/M).

For most applications, the retardation factor, R , is assumed to be constant and all associated reaction mechanisms are assumed to be reversible. These assumptions are based on a more global assumption that the chemical environment along the flow path remains constant for a given type of porous media or material.

Use of the linear sorption isotherm model in the transport equation results in an expression whereby the diffusion and the advection terms are divided by the retardation factor as follows:

$$D_i^* \left(\frac{\partial^2 C_i}{\partial x^2} + \frac{\partial^2 C_i}{\partial y^2} + \frac{\partial^2 C_i}{\partial z^2} \right) - v_x \frac{\partial C_i}{\partial x} - v_y \frac{\partial C_i}{\partial y} - v_z \frac{\partial C_i}{\partial z} = R_i \frac{\partial C_i}{\partial t} \quad (P.28)$$

or as it is more commonly written,

$$\frac{D_i^*}{R_i} \left(\frac{\partial^2 C_i}{\partial x^2} + \frac{\partial^2 C_i}{\partial y^2} + \frac{\partial^2 C_i}{\partial z^2} \right) - \frac{v_x}{R_i} \frac{\partial C_i}{\partial x} - \frac{v_y}{R_i} \frac{\partial C_i}{\partial y} - \frac{v_z}{R_i} \frac{\partial C_i}{\partial z} = \frac{\partial C_i}{\partial t} \quad (\text{P.29})$$

where D_i^* = apparent or effective diffusion coefficient for i^{th} species (L^2/T)

C_j = concentration of i^{th} species (M/L^3)

R_i = retardation factor for i^{th} species.

Note that a retardation factor of 2 will reduce the diffusion coefficient and average linear velocities by half; a factor of 10 will reduce them by an order of magnitude.

The distribution coefficient is affected by both the surface chemistry properties of sediment minerals as well as the solution chemistry of the pore fluids. Vadose zone sediments do not exhibit much variation beyond pH or cation exchange capacity (Ames and Serne 1991), which are functions of mineral surface properties. Pore fluid chemistry (e.g., pH, Eh, and dissolved solids) in porous materials is controlled by mineral-fluid reactions and is generally dominated by the minerals present, particularly for systems with high solid-to-liquid ratios. Also, both vadose zone and groundwater pathways are inhomogeneous, which can cause some variation in sorption properties with distance. For these reasons, as well as the lack of site-specific geochemical data, it is generally accepted that a constant retardation factor model based on a range of empirically determined values is satisfactory for performance assessment calculations if sufficient conservatism is included (Ames and Serne 1991).

Decay. No additional information or equation development included because material in body of document was sufficient.

P.2 Section 3.3.1, Radionuclides and Chemical Inventories

P.2.1 Daughter Product Ingrowth

In the simulation of transport within the vadose zone, each transport group is modeled using a unit concentration and neglecting radioactive decay. The inventory and radioactive decay for each radionuclide is then applied to the results to calculate groundwater and well concentrations. In cases where short-lived daughter products are produced and can be expected to be in secular equilibrium with the parent, the daughter is assumed to be present for the purpose of calculating the dose. However, for

species with long-lived daughter products, the calculational approach does not allow for ingrowth of long-lived daughter products during the transport simulation. These daughter products may have transport properties in the vadose zone that are different from the parent such that the transport of the daughter may be accelerated or retarded compared to the parent radionuclide.

One radionuclide for which the ingrowth of daughters needs to be considered is neptunium-237. The dose impact of the daughter products can be bounded by an assumption that the daughters exist in secular equilibrium with the parent radionuclide. Under this assumption, the doses from daughter products are approximately as large as those from neptunium-237, resulting in approximately a factor of two increase in the drinking-water dose at longer time frames (>200,000 years). Because of the potential significance of the daughters in this case, the issue has been examined in greater detail.

Neptunium-237 decays as follows:

neptunium-237 ($t_{1/2} = 2.2\text{E}6$ yr) decays by alpha to

protactinium-233 ($t_{1/2} = 27$ day) decays by beta to

uranium-233 ($t_{1/2} = 1.62\text{E}5$ yr) decays by alpha to

thorium-229 ($t_{1/2} = 7340$ yrs) which then decays through eight short half-life decays, eventually reaching bismuth-209 which is stable.

The additional dose impact is primarily attributed to the activity of thorium-229 and its short half-life daughters. The question for the performance assessment is whether the thorium-229 will grow into equilibrium as the neptunium-237 decays during transport from the grout to the groundwater. Any uranium-233 or thorium-229 either initially in the grout or produced in the grout due to radioactive decay will be held effectively within the grout due to the sorption (model $R_d = 2625$ versus 125 for neptunium-237). After release from the grout, uranium-233 generated from neptunium-237 decay would be transported more rapidly than the neptunium-237 in the soil column (model $R_d = 0$ versus $R_d = 3.0$ for neptunium-237). This would be a beneficial effect since the daughter would be transported out of the vadose zone and appear in the well primarily as uranium-233, which has a much lower dose impact than thorium-229. If the uranium-233 undergoes decay to thorium-229 in the soil column, the thorium-229 will be strongly sorbed to the soil ($R_d = 21$ versus 3 for neptunium-237) and much of it will decay prior to reaching the well.

A very conservative treatment would be to assume that the neptunium-237 and its daughter products transport at the same rate in the soil column and that the thorium-229 begins ingrowth at the point of release from the grout. This neglects the beneficial effect of more rapid transport of uranium-233 and the strong sorption of thorium-229 in the soil. The half-lives of the radionuclides can be used to simulate the decay and ingrowth of daughters over time. The travel time of neptunium-237 in the vadose zone is approximately 30,000 years. Figure P.3 shows the ingrowth of uranium-233 and thorium-229 over a

Figure P3. Ingrowth of Neptunium-237 Daughter Products as a Function of Time

100,000-year period. At secular equilibrium, the activities of thorium-229 and neptunium-237 would be equal and the resulting doses would be about double, with the majority of the increase being due to the thorium-229 and daughters. After 30,000 years the thorium-229 is about 8% of the parent activity and at 100,000 years it is 31%. Under these conditions, the drinking-water dose at long times would be increased by approximately 8%. Even assuming a 100,000-year travel time, the dose would only be increased approximately 31%. Thus, even without the beneficial effects resulting from greater mobility as uranium-233 and lesser mobility as thorium-229, the increases in dose are not large.

Based on this analysis, it was concluded that the ingrowth of neptunium-237 would not have a significant influence on the dose at the well. Therefore, doses calculated for neptunium-237 in groundwater-related scenarios do not include the long-lived daughter products. Note that formation of long-lived daughter products is considered in analysis of the intruder and flood scenarios where the inventory is decayed within the grout and is then disturbed and distributed for the dose calculation.

P.3 Section 3.3.3.1, Initial Release Model For Grout

P.3.1 Diffusion in Grout

P.3.1.1 Review of Available Data on Release of Iodine-129 and Technetium-99 from Grout

Technetium-99 and iodine-129 are the most important radionuclides relative to the performance objectives for groundwater-related scenarios. This section reviews the data available on the release of iodine and technetium from grout waste forms. The basis for neptunium sorption is provided in Section P.2.2.1. The various wastes for which grouts have been tested for release of technetium and iodine are shown in Table P.1. The current formulation for Tank 106-AN waste (currently the first tank planned for grouting) is also included for comparison. The form of the tracers used in the leach tests is shown as well.

All leach data presented here used groundwater as the leachant. Data has also been collected using deionized water. Results obtained when using deionized water are often different than results obtained when using groundwater. Sometimes release is retarded and other times it is accelerated, but the results are within a factor of 10 of the groundwater leachant results.

The data for technetium and iodine release from phosphate/sulfate waste (PSW) grout are fairly comprehensive. Experiments have been conducted with two different specimen sizes and two different waste form loadings, and the leaching has been done using two different test configurations. Table P.2

Table P.1. Dry Blend Formulations and Tracers Used in Technetium and Iodine Leach Tests

	PSW (70% phosphate, 30% sulfate)	CRW	T-106-AN (actual waste)	DSSF	Current 106-AN Formulation
Dry Blend Constituents (wt%)					
Portland cement type I/II	41	42	5	6	21
Class F fly ash	40	40	47.5	47	68
Attapulgit clay	11	--	--	--	11
Indian Red pottery clay	8	8	--	--	--
Calcium hydroxide	--	10	--	--	--
Ground blast furnace slag	--	--	47.5	47	--
Mix Ratio (g dry blend/ L waste)	840	840	1080	1080	1007
Tracer Form					
	^{125}I as NaI, (I^-)	^{125}I as NaI, (I^-)	Unknown.	^{125}I as NaI, (I^-)	
	^{99}Tc as NH_4	^{99}Tc as NH_4	Actual waste	^{99}Tc as NH_4	
	TcO_4 , (TcO_4^-)	TcO_4 , (TcO_4^-)		TcO_4 , (TcO_4^-)	

Table P.2. Summary of 223-Day Leach Test Results for Iodine and Technetium in PSW Grout (Serne et al. 1989a)

Tracer Isotope	Tracer Concentration (mCi/L)	Sample Size	Test Configuration	
			ANS 16.1 De (cm ² /s)	Static De (cm ² /s)
¹²⁵ I	0.05	small	$6.1 \pm 5.7 \times 10^{-11}$	$5.3 \pm 0.6 \times 10^{-9}$
¹²⁵ I	0.05	large	1.3×10^{-11}	--
¹²⁵ I	0.5	small	$1.2 \pm 0.3 \times 10^{-10}$	$3.43 \pm 2.30 \times 10^{-9}$
¹²⁵ I	0.5	large	1.3×10^{-11}	--
⁹⁹ Tc	0.08	small	$1.4 \pm 0.9 \times 10^{-11}$	$3.0 \pm 0.9 \times 10^{-11}$
⁹⁹ Tc	0.08	large	2.3×10^{-11}	--
⁹⁹ Tc	0.20	small	$2.8 \pm 2.6 \times 10^{-11}$	$3.9 \pm 0.4 \times 10^{-11}$
⁹⁹ Tc	0.20	large	6.8×10^{-11}	--

provides a summary of results. Note that the effective diffusivities provided here are based on the concentration in the bulk grout rather than in the pore fluid. As can be seen in Table P.2, different effective diffusivities for I⁻ are obtained in the two different leach test configurations. The diffusivities obtained in static leach tests are approximately 30 to 100 times greater than those obtained in the ANS 16.1 leach test. This difference probably is not due to formation of carbonate on the sample because other species do not have significantly different behavior between the two types of tests (for example, see ⁹⁹Tc results in Table P.2). It is possible that the release of I⁻ is affected by the higher leachant pH in the static test. The results for TcO₄⁻ indicate that the effective diffusivity is 2 to 5 times greater in a larger sample. The reason for this difference is not known.

The leach results for technetium and iodine in cladding removal waste (CRW) grouts are shown in Table P.3. For this waste, tests have been run with a constant waste loading (0.5 mCi/L I⁻ and 0.036 mCi/L TcO₄⁻) and a single sample size, but the leaching has been conducted in several different configurations. In addition to the data shown in Table P.3, data on release from crushed grout has also been obtained. The leach tests were conducted for periods of 200 to 425 days with two to four replicates. As with PSW results, I⁻ leaches faster than the TcO₄⁻. Flow-through tests produced the most rapid release, while ANS 16.1 tests produced the slowest release. The possibility of advection within the grout and the possible difference in boundary conditions compared to a static leach test introduces some uncertainty in the meaning of results for the flow-through tests. Linear pore velocities in the flow-through tests ranged from 1.7×10^{-3} cm/h to 2 cm/h, while the calculated effective diffusivities varied by about a factor of 5.

Table P.4 summarizes information available on grout produced using actual waste from Tank 106-AN. The tests were conducted over a period of only 46 days and only a small number of specimens were tested. In addition, the analysis for iodine-129 and technetium-99 in the waste prior to grouting and in leachates presented a major challenge. Iodine-129 was present as a very minor component

Table P.3. Summary of Leach Test Results for Iodine and Technetium in CRW Grout (Serne and Wood 1990)

Test Configuration	Effective Diffusivity (cm ² /s)	
	¹²⁵ I ⁻	⁹⁹ TcO ₄ ⁻
ANS 16.1	0.6 to 1.1 x 10 ⁻⁹	1.8 to 3.4 x 10 ⁻¹²
Static	1.6 to 1.9 x 10 ⁻⁹	1.7 to 1.8 x 10 ⁻¹¹
Flow-Through	2.5 to 3.4 x 10 ⁻⁸	0.3 to 1.2 x 10 ⁻¹⁰
Flow-Through, Packed in Soil	0.8 to 4.1 x 10 ⁻⁸	0.6 to 3.3 x 10 ⁻¹⁰

Table P.4. Summary of Leach Results for Tank 106-AN Grout Leach Results: Test Duration 46 Days (Serne et al. 1989b)

Isotope	Diffusivity Obtained in Leach Test Configuration	
	ANS 16.1 (cm ² /s)	Static (cm ² /s)
¹²⁹ I	3.1 x 10 ⁻⁸	4.5 to 7.3 x 10 ⁻⁸
⁹⁹ TcO ₄ ⁻	3.6 x 10 ⁻⁸	4.3 to 6.4 x 10 ⁻⁸

(activity seven orders of magnitude lower than cesium-137, five orders of magnitude lower than strontium-90). The technetium data are also suspect. Original inventory was rather low and reproducibility of measured values in replicate samples was not good. In general, the data reported in Table P.4 are likely biased towards higher-than-actual effective diffusivities because of the analytical difficulties. The approach taken was to assume that analytical results in leachates that were below detection limits were in fact legitimate values.

ORNL also performed leach tests with deionized water and simulated Tank 106-AN grouts. They found technetium to leach about 350 times slower than the leach rate determined at Hanford (Tallent et al. 1988).

Data for double-shell slurry feed (DSSF) grouts produced using the dry blend shown in Table P.1 are quite extensive. A summary of the data is provided in Table P.5. Technetium leaching over a 154-day period was studied using specimens of five different sizes and five different waste loadings. Iodine leaching was studied over a 91-day period using one specimen size with three different iodine waste loadings. Both the ANS 16.1 and static leach test configurations were used for each isotope. As in testing with other wastes, I⁻ leaches much faster than TcO₄⁻ in the DSSF tests. Unlike testing with other wastes, diffusivities obtained in static tests are not markedly higher than they are in the ANS 16.1 tests. The leach rate does not appear to be a function of waste loading in the grout for I⁻.

Table P.5. DSSF Grout: Leach Data for I⁻ (91-day tests) and TcO₄⁻ (154-day tests) Using Static and ANS 16.1 Test Configurations (Serme et al. 1992)

Isotope	Concentration (mCi/L)	Diffusivity Obtained in Leach Test Configuration	
		ANS 16.1 (cm ² /s)	Static (cm ² /s)
I ⁻	0.5	3.4×10^{-8}	$3.7 \pm 0.3 \times 10^{-8}$
I ⁻	5.0	4.2×10^{-8}	$8.9 \pm 3.8 \times 10^{-8}$
I ⁻	50.0	3.4×10^{-8}	$4.8 \pm 0.6 \times 10^{-8}$
TcO ₄ ⁻	0.1	1.8×10^{-10}	6.3×10^{-10}
TcO ₄ ⁻	0.3	3.2×10^{-10}	7.7×10^{-11}
TcO ₄ ⁻	1.0	7.0×10^{-10}	1.4×10^{-9}
TcO ₄ ⁻	3.0	6.7×10^{-10}	1.0×10^{-9}
TcO ₄ ⁻	10.0	3.0×10^{-9}	6.1×10^{-10}
Data at various sample sizes:			
TcO ₄ ⁻	0.3	$4.0 \pm 3.1 \times 10^{-9}$	--

On the other hand, TcO₄⁻ leach data suggest some dependence upon technetium inventory. The larger the TcO₄⁻ inventory, the larger the calculated effective diffusivity. The separate tests for technetium release as a function of specimen size showed no effects that could be attributed to specimen size, but the results are not consistent with separate inventory tests on small samples conducted at the same TcO₄⁻ loading (0.3 mCi/L). The technetium leach rate from the various sizes of specimens is about a factor of 10 higher than the technetium inventory samples that had the same inventory. Based on this information, it is concluded that any given grout mixing/curing campaign can add about one order-of-magnitude variation in leach results for minor contaminants. Additional detail is provided in Serme et al. (1992).

Based on the leach data collected on various grouts, an estimate of the expected effective diffusivities for iodine and technetium was made as shown in Table P.6. Some conservatism exists in these numbers because the calculated effective diffusivity is observed to decrease with the duration of the leach test. However, experimental work (Lokken 1992) has indicated that the diffusion coefficient for nitrate in grout cured at high temperature over long time periods increases to values approaching 1×10^{-6} cm²/s. Because of this, the diffusion coefficients have been degraded prior to their application in the model to provide a diffusivity for iodine of 1×10^{-6} cm²/s. Finally, in the numerical model, the concentration driving force for diffusion is defined in pore volume of the grout rather than the total grout volume. Therefore, the diffusivities are adjusted for use with the pore solution driving force prior to application in the compliance case models. A summary of the diffusivities selected and used is provided in Table P.6.

Table P.6. Selection of Effective Diffusion Coefficients for Compliance Case Models

Contaminant	Selected Effective Diffusivity (cm ² /s) ^(a)	Degraded Diffusivity Assuming High-Temperature Curing (cm ² /s) ^(a)	Compliance Case Diffusivity (cm ² /s) ^(b)
I ⁻	5.0 x 10 ⁻⁸	1.0 x 10 ⁻⁶	5.8 x 10 ⁻⁷
TcO ₄ ⁻	1.0 x 10 ⁻⁸	2.1 x 10 ⁻⁷	1.2 x 10 ⁻⁷ (c)

(a) Concentration driving force based on grout volume.

(b) Concentration driving force based on grout pore volume.

(c) Implemented in model as a diffusivity of 5.8 x 10⁻⁷ cm²/s and a distribution coefficient of 2 ml/g.

P.3.2 Sorption in Grout

P.3.2.1 Review of Available Data on Neptunium Leaching from Cement and Cement Leachate/Sediment Adsorption

At this time, there is not any Hanford grout-specific data for neptunium release or adsorption from leachate onto Hanford sediments. Values used in the performance assessment were chosen to be conservative estimates based on general literature. Because of the importance of neptunium-237 in the long-term performance assessment calculations, the data that is available for neptunium is discussed here to provide some insight into the conservative nature of the assumptions regarding the mobility of neptunium-237.

At present, neptunium has not been spiked into any of the simulated Hanford grout samples that have been leach tested. The neptunium activity in actual Hanford grouts (phosphate-sulfate and Tank 106-AN) and their leachates have also not been measured although it is appropriate to state that neptunium activities in leachates had to be low because rather detailed nuclide analyses did not detect any neptunium activity in actual grout leachates. Tank 106-AN leachates were treated with wet chemical techniques to specifically concentrate and separate various actinides for alpha counting, but only plutonium-239 and -240, americium-241, and curium-244 were found in some of the samples at very low concentrations (Serne et al. 1989).

There have been four neptunium-Hanford sediment adsorption studies documented. In the first, Bensen (1961) examined the adsorption on minerals of radionuclides in Hanford reactor effluent cooling water. One of the radionuclides studied was neptunium-237, which was adsorbed on 25 different com-

mon sulfide, silicate and carbonate minerals, crushed to particle size 0.05 to 0.25 mm, in equilibrium tests with trace amounts in Columbia River water at 80°C. According to Bensen, neptunium was adsorbed poorly or not at all by the minerals tested. The test conditions are not directly relevant to Hanford grout leachate but the data do suggest that neptunium may be mobile. Routson et al. (1975, 1976) determined neptunium R_d values for a Washington sand. The properties of this soil are given in Table P.7. The neptunium R_d values are given in Table P.8. Pre-equilibrations of the soils with nonradioactive solutions prior to contact with the traced solution containing neptunium-237 were carried out. Calcium nitrate and sodium nitrate salts were used as calcium and sodium ion sources. Cation exchange of NpO_2^+ cannot be the principal adsorption mechanism because Na^+ concentration essentially does not affect the neptunium R_d values from no sodium competition to 3.0M Na^+ competition. Calcium has some effect on the neptunium R_d , but much less than there would be if neptunium adsorption were due to ion exchange.

Sheppard et al. (1976) determined neptunium distribution coefficients on two Washington soils. The distilled water-trace neptunium-237 solutions and soils were equilibrated over long periods of time to obtain a rate of change per month in the distribution coefficient values. The 50-day values are given in Table P.9. A positive value for the monthly change in the distribution means an increase in the size of the

Table P.7. Properties of Hanford Soil (Routson et al. 1976)

Soil	CaCO_3 , mg/g	Silt, wt%	Clay, wt%	CEC, meq/100 g	pH
Washington Soil (Burbank sandy loam)	0.8	10.1	0.5	4.9	7.0

Table P.8. Neptunium R_d (ml/g) as a Function of Soil and Solution (Routson et al. 1976)

Soil	Calcium		Sodium	
	0.002 M	0.2 M	0.015 M	3.00 M
Washington	2.37	0.36	3.9	3.2

Table P.9. Neptunium 50-Day Distribution Values Computed from Sheppard et al. (1976)

Soil Identity	Neptunium Distribution, ml/g	Monthly Change in Distribution, %
Burbank loamy sand	15.4	+48
Ritzville silt loam	20.2	+28

distribution value. The distribution was determined in the same way that a R_d value is determined, but does not have the connotation that equilibrium has been attained.

The neptunium R_d value of about 3.9 ml/g was given by Routson et al. (1975, 1976) for the Burbank sandy loam without sodium in the solution. Sheppard et al. (1976), apparently for the same conditions, gives a neptunium 50-day distribution coefficient value of 15.4 ml/g for Burbank sandy loam and states that this value is increasing at the rate of +48%/month. At 100 days, the distribution coefficient was approximately 50 ml/g on the Burbank sandy loam. The differences between the neptunium R_d of Sheppard and Routson are disconcerting given the fact that Sheppard's soil sample was obtained from Routson. However, Sheppard showed that his Burbank sample contained 21.2% silt and 2.8% clay with a pH of 8.1 and a cation-exchange capacity of 5.94 meq/100 g compared to Routson's Burbank soil sample (see Table P.9). Sheppard's Burbank sample must have contained calcite (CaCO_3) to attain a pH of 8.1. There is no evidence in Sheppard et al. (1976) that his soil samples were pre-equilibrated in any way with the nonradioactive solution before the neptunium tracer was added, or that a blank solution without the soil was run with the soil equilibrations for reference and to observe container adsorption. In addition, Sheppard reported that his neptunium-237(V) in the aqueous phase equilibrating with Ritzville soil could be partially filtered on Whatman number 50 filter paper. Routson, on the other hand, reported that upon filtering previously centrifuged samples of solution containing neptunium and in contact with Burbank or South Carolina subsoil through 0.01 and 0.45 μm filters, no evidence of colloidal neptunium-237 was found. This is further evidence that Sheppard's high neptunium distribution values require further elucidation in light of Routson's results.

Serne et al. (1993) measured neptunium adsorption onto a sediment from Hanford's 200 West Area. The sediment's physical/chemical characteristics are shown in Table P.10. Several adsorption tests were performed using three distinct solutions. Two solutions represented leachates from solid wastes that included typical cardboard, paper, rubber, cloth, etc. The two leachates contained significant concentrations, 250 to 500 mg/L dissolved organic carbon. One of the leachates had a pH of 12, resulting from equilibration with crushed cement. Aside from the enriched organic content and lower sodium, nitrate, and other salts present in Hanford grout leachate, this solid waste leachate in contact with cement is quite similar to DSSF grout leachate. The third solution used in adsorption tests was an uncontaminated Hanford groundwater. Distribution coefficients for these three solutions traced with NpO_2^+ ions over a period from 5 to 44 days of contact are shown in Table P.11.

The data in Table P.11 show that NpO_2^+ is not soluble in a high pH environment in the presence of Hanford sediment. (Most of the neptunium precipitated out of blank test tubes as well as tubes containing sediment.) These data lead us to conclude that neptunium will likely remain strongly bound within the grouts and will leach at very slow rates as does the other actinides studied (uranium, americium, plutonium; see Serne et al. 1989 and Serne and Wood 1990). Any neptunium that does leach into the highly alkaline grout leachate should react with Hanford sediment and adsorb. The competition of the high concentrations of sodium and potassium (up to 600 mg/L and 60 mg/L, respectively) should not lower the R_d value significantly based on the Routson et al. (1976) work on the effects of calcium and

Table P.10. Characteristics of the 200 West Area Hanford Sediment

Sand, %	Silt, %	Clay, %	CaCO ₃ , %	TOC, %	CEC, meg/100 g	pH	Mineralogy of < 2 mm, %
87	7	6	2.00	0.2	5.2 ± 2.0	7.9	Plagioclase 26 Quartz 43 Mica/Illite 7 Kaolinite 7 Smectite 3

Table P.11. Neptunium Rd Values (ml/g) for Various Solutions Contacting Hanford Sediment (values shown as ± indicate one standard deviation based on three samples)

Solution	5 days	44 days	Average
Wood/paper leachate	6 ± 2	20 ± 7	13 ± 7
All waste/cement leachate	200 ± 70	> 3,000	> 1,600
Groundwater	14 ± 3	29 ± 4	22 ± 9

sodium competition (see Table P.8) and the Staunton, Clay and Rees (1990) work showing that sodium does not reduce neptunium adsorption even at very high concentrations (0.1 M).

An Rd value as large as 100 ml/g seems justified for highly alkaline solutions contacting Hanford sediments. For more neutral pH and dilute waters such as groundwater, a range of 10 to 20 ml/g would be defensible based on Sheppard et al. (1976) and Serne et al. (1993). A conservative value of 3 ml/g was used in the performance assessment calculations for neptunium adsorption onto Hanford sediments.

Meyer, Arnold and Case (1985) show that NpO_2^+ adsorption onto minerals in the presence of carbonate is reduced to values of one-half to one-third those when carbonate is not present. Bidoglio, DePlano and Chatt (1983) suggest that NpO_2^+ complexes with carbonate/bicarbonate are relatively weak. In the Hanford grout environment, carbonate is effectively removed in reactions with the Ca(OH)_2 that forms during cement hydration. Thus, we might expect neptunium adsorption to be high in the very near field surrounding the grout vault.

Bondietti (1982) found that neptunium(V), $[\text{NpO}_2^+]$, adsorption under slightly alkaline pH conditions (pH = 8) onto shale was greater than uranium(VI) and plutonium(IV), $\text{Rd} = 70 \text{ ml/g}$, whereas under slightly acidic conditions, pH = 5.8, neptunium adsorption was much lower than uranium(VI) and plutonium(IV) at $\text{Rd} = 5 \text{ ml/g}$. Girvin et al. (1991) also found the neptunium(V) adsorption dramatically increased on amorphous iron oxyhydroxides as pH was raised above a value of six.

Allard et al. (1982) found that neptunium adsorption, as well as most metals that hydrolyze, increased dramatically when the neutral species NpOOH^0 [for neptunium(V)] and Np(OH)_4^0 [for neptunium(IV)] predominates in solution.

One study of neptunium adsorption directly onto Portland cement, 70-year-old weathered concrete, sulfate resistant cement, high alumina cement, silica cement, fly ash and blast furnace slag was found. In all cases the solution was simulated pore waters based on the chemical composition of waters in equilibrium for 4 months with crushed material. The pore waters all had pH values between 12.4 and 13.4 and were predominately at potassium, sodium rich hydroxide solution. Crushed cements between 0.090 and 0.125 mm (very fine sand-sized) were contacted with simulated pore waters that had been traced with $1.9 \times 10^{-7}\text{M}$ neptunium(V). Adsorption ratios were measured after 0.25, 1, 6, 42 and 90 days. The tests were performed in controlled atmosphere chambers free of CO_2 . The solid-to-solution ratio was 0.02-g cement/ml of solution. After one day of contact the neptunium adsorption reached a steady-state value of 1,000 to 6,000 ml/g with an average for the different cements of about 2,000 ml/g. Details are found in Höglund et al. (1985).

The latter article suggests that neptunium solidified in cement is not readily available to leaching even if it was placed in the cement in its most soluble neptunium(V) form. It is not clear whether the neptunium is actually adsorbed by cement hydration products, precipitates as insoluble phases or co-precipitates with hydration phases. We next review articles where neptunium is mixed with solidifying agents and leached by traditional leach tests.

Only one investigation was found where the leaching of neptunium from cement waste forms was discussed. The article, Ewart et al. (1992), discusses the leaching of neptunium(IV) from concrete under reducing conditions expected in a deep-geologic repository. At an Eh value of -400mv, the equilibrium neptunium solution concentration at pH values ranging from 9.8 to 13.0 was $8 \times 10^{-9}\text{M}$. The data suggest that Np(OH)_4 solid is controlling the release of neptunium and that anionic complexes such as Np(OH)_5^- cannot be very stable. Rai and Ryan (1985) agree that Np(OH)_5^- must not be a strong complex. Unfortunately, the work with neptunium(IV) solids and reduced solutions may not be relevant to Hanford grout solidification and subsurface disposal in vadose zone sediments. Oxidizing conditions that will allow NpO_2^+ , [Np(V)], to predominate are expected. Neptunium(V) is much more soluble and may leach more rapidly from grout. For example, Keiling and Marx (1991) took leachate from a Portland cement-saturated salt water test and added $\text{NpO}_2(\text{OH})$ solid in excess. At equilibrium (pH = 12.3), the neptunium solution concentration was between 2 and $9 \times 10^{-4}\text{M}$, almost 5 orders of magnitude larger than the Ewart et al. results on neptunium(IV) dissolving out of concrete. Similar redox sensitive results for neptunium release from glass and subsequent migration of leached neptunium through glauconite sand were found by Bidoglio, Avogadro and DePlano (1985). The leach rate of neptunium from glass under oxidizing conditions was ten times greater than under reducing conditions.

In summary, a distribution coefficient of 10 to 20 ml/g is expected in the vadose zone soils. However, because of the limited data available a value of 3 ml/g has been selected to assure the analysis is conservative. In the grout, the distribution coefficient is likely in the range of 1,000 to 6,000 ml/g based

on the work by Höglund et al. (1985). However, because the data is not directly applicable to double-shell tank waste grout, a conservative value of 125 ml/g has been selected within the grout. Although similar sorption may occur within the concrete as well, no sorption has been assumed in the concrete regions of the problem.

P.4 Section 3.6.5.3, Sensitivity Cases

This text discusses Cases 2.3C and 2.3D in Table 3.46. Differences between the central sensitivity case and Case 2.3C and 2.3D are listed below. Because of these differences, it is not appropriate to compare the results of these two cases to those of the central sensitivity case.

- The asphalt and concrete do not have discrete cracks as are present in the central sensitivity case.
- The grout diffusivity in Cases 2.3C and 2.3D ($5.78 \times 10^{-7} \text{ cm}^2/\text{s}$) has been adjusted to account for the concentration driving force being in the pore solution, which reduces the magnitude applied in the central sensitivity case ($1.0 \times 10^{-6} \text{ cm}^2/\text{s}$) by a factor of 0.5781 (the volume fraction pore solution of grout).
- The saturated hydraulic conductivity of the barrier is $3 \times 10^{-5} \text{ cm/s}$ (rather than $1 \times 10^{-20} \text{ cm/s}$) in the asphalt barrier, simulating a 1-mm crack every meter.
- The asphalt barrier is given backfill soil water retention properties.
- The asphalt barrier is assigned a diffusivity of $4.2 \times 10^{-9} \text{ cm}^2/\text{s}$ compared to $1 \times 10^{-10} \text{ cm}^2/\text{s}$ in the central sensitivity case.
- In addition, the simulations were run only for 25,000 years to reduce the computation time required.

P.5 Section 4.1.1, Vadose Zone Results

In the performance assessment, results were presented for the moisture content and Darcy velocities for the central sensitivity case at 10,000 years. A number of plots are provided here with additional data for the central sensitivity case at other times. A contour plot of the moisture content in the system at 100 years is shown in Figure P.4. The corresponding vertical and horizontal Darcy velocities at 100 years are provided in Figures P.5a and P.5b. Figure P.6 shows the moisture content contours at 1,000 years and Figure P.7 provides details of the moisture content in the upper region of the system. The corresponding horizontal and vertical Darcy velocities at 1,000 years are provided in Figures P.8a and P.8b. Figures P.9, P.10a, and P.10b correspond to Figures 4.1, 4.2A, and 4.2B, respectively, shown in Chapter 4 and are

Figure P.4. Central Compliance Case (Case 1.0): Moisture Content Contours for the Vadose Zone at 100 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

Figure P.5a. Central Compliance Case (Case 1.0): Contour Plots of the Horizontal Darcy Velocities at 100 Years

Figure P.5b. Central Compliance Case (Case 1.0): Contour Plots of the Vertical Darcy Velocities at 100 Years

Figure P.6. Central Compliance Case (Case 1.0): Moisture Content Contours for the Vadose Zone at 1,000 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

Figure P.7. Central Compliance Case (Case 1.0): Details of the Moisture Content Contours in Upper Vault and Surrounding Vadose Zone Region at 1,000 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

provided here for ease of comparison only. Figure P.11 provides additional details of the upper region of the system in the central compliance case. Figure P.12 provides the moisture content contours for the central compliance case at 50,000 years. Figures P.13a and P.13b provide the corresponding Darcy velocities at 50,000 years.

Figure P.8a. Central Compliance Case (Case 1.0): Contour Plots of the Horizontal Darcy Velocities at 1,000 Years

Figure P.8b. Central Compliance Case (Case 1.0): Contour Plots of the Vertical (right) Darcy Velocities at 1,000 Years

Figure P.9. Central Compliance Case (Case 1.0): Moisture Content Contours for the Vadose Zone at 100 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

Figure P.10a. Central Compliance Case (Case 1.0): Contour Plots of the Horizontal Darcy Velocities at 10,000 Years. Same as Figure 4.2A in main document.

Figure P.10b. Central Compliance Case (Case 1.0): Contour Plots of the Vertical (right) Darcy Velocities at 10,000 Years. Same as Figure 4.2B in main document.

Figure P.11. Central Compliance Case (Case 1.0): Details of the Moisture Content Contours in Upper Vault and Surrounding Vadose Zone Region at 10,000 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

Figure P.12. Central Compliance Case (Case 1.0): Details of the Moisture Content Contours in Upper Vault and Surrounding Vadose Zone Region at 50,000 Years. Values at the right indicate the volume fraction moisture at which contours are drawn.

Figure P.13a. Central Compliance Case (Case 1.0): Contour Plots of the Horizontal Darcy Velocities at 50,000 Years

Figure P.13b. Central Compliance Case (Case 1.0): Contour Plots of the Vertical (right) Darcy Velocities at 50,000 Years

P.5.1 Section 4.1.1.2, Release to Groundwater

A plot of the fractional release per year by transport group was provided in Chapter 4 (Figure 4.6). The same information is provided in Figure P.14 except that it is plotted as the cumulative percent of mass released to the aquifer. At a value of 100 all of the mass has been released. The actual values exceed the value of 100 due to a positive mass balance error. This error is discussed in Section P.6.

Figure P.14. Cumulative Percent of Mass Released to the Aquifer. Iodine-129 corresponds to transport grouping 1A, technetium-99 corresponds to grouping 2A, neptunium-237 corresponds to grouping 3C, and uranium-238 corresponds to group 4A. Figure does not include radioactive decay.

Similar information is contained for transport group 1A (iodine-129) in Figure P.15. However, this figure is plotted on a linear-linear scale and provides the fraction released from a region of the engineered system rather than release to the water table, and information on the amount of material leaving the region by diffusive or advective mechanisms. The region is defined by a rectangle that passes along the boundary between the top of the asphalt barrier and the gravel and then down from the top outside corners of the asphalt barrier. Rather than following the slope of the wall, the region drops straight down through the sloping asphalt barrier wall and passes between the asphalt barrier and side of the catch basin. The bottom of the flux region is placed between the asphalt barrier and the soil.

Figure P.15. Case 1.0 (central compliance case): Fractional Release of Group 1A (iodine-129) from Region of Engineered System by Diffusive and Advective Mechanisms

A similar plot is provided in Figure P.16, only it is drawn for transport group 2A (technetium-99). As can be seen in the plots, the release from this region is very nearly split evenly between diffusive and advective mechanisms.

Figure P.16. Case 1.0 (central compliance case): Fractional Release of Group 2A (technetium-99) from Region of Engineered System by Diffusive and Advective Mechanisms

Fractional release by diffusion and advection from the region of the engineered system is provided for compliance cases: Case 1.1 (delayed cracking), Figures P.17 and P.18; Case 1.2 (no HDPE flow path), Figures P.19 and P.20; and Case 1.3 (composite model), Figures P.21 and P.22.

Figure P.17. Case 1.1 (delayed cracking): Fractional Release of Group 1A (iodine-129) from Region of Engineered System by Diffusive and Advective Mechanisms

Figure P.18. Case 1.1 (delayed cracking): Fractional Release of Group 2A (technetium-99) from Region of Engineered System by Diffusive and Advective Mechanisms

Figure P.19. Case 1.2 (no HDPE flow path): Fractional Release of Group 1A (iodine-129) from Region of Engineered System by Diffusive and Advective Mechanisms

Figure P.20. Case 1.2 (no HDPE flow path): Fractional Release of Group 2A (technetium-99) from Region of Engineered System by Diffusive and Advective Mechanisms

Figure P.21. Case 1.3 (composite model): Fractional Release of Group 1A (iodine-129) from Region of Engineered System by Diffusive and Advective Mechanisms

Figure P.22. Case 1.3 (composite model): Fractional Release of Group 2A (technetium-99) from Region of Engineered System by Diffusive and Advective Mechanisms

P.6 Section 4.1.2, Dose Results for Groundwater Pathway

P.6.1 Mass Balance Information for Compliance Cases

Water was added to computational cells within the compliance case simulations to simulate water vapor diffusion. As the result of a default feature of the code (which was unknown at the time), the water was added at the concentration of the cells rather than as clean water. This resulted in a mass balance error which is always positive and is most severe when water vapor diffusion rates and concentrations in the affected nodes are the highest. The mass balance is computed for the problem as a whole, as well as for a region containing much of the engineered system. The boundary for the mass balance within the engineered system is a rectangular area, the top of which follows the boundary between the asphalt barrier and the gravel. The bottom of the rectangle is between the asphalt barrier and the underlying soil. The sides are vertical and are in line with the backfill soil/asphalt barrier interface at the top corners of the asphalt barrier. Because the vault wall surface and asphalt barrier slope outwards, the sides of the rectangular area pass from the outside of the asphalt barrier at the top corner, to the catch basin/asphalt barrier interface near the lower corners. This region is referred to as the "engineered system" even though it excludes some areas of the asphalt barrier. All of the vapor diffusion sources are included within this region.

The mass balance over time for the central compliance case is illustrated in Figure P.23 for the entire problem as well as for the engineered system. The normalized total mass (NTM) which is plotted is defined as:

$$NTM = \frac{(X_{\text{system}} + X_{\text{flux}})}{(X_{\text{system initial}})} \quad (\text{P.30})$$

where X_{system} = total mass within boundary at time of interest

X_{flux} = integral of flux across the boundary over time

$X_{\text{system initial}}$ = initial mass within boundary.

The mass balance error results for Cases 1.1 (delayed cracking), 1.2 (no HDPE flow path), and 1.3 (composite model) are shown in Figures P.24, P.25, and P.26, respectively. The mass balance errors in Figures P.23, P.24, and P.25 indicate similar mass balance errors in that the errors occur in the engineered system, always increase with time, and are of similar magnitude. However, Figure P.26, which shows the mass balance obtained using the composite model for concrete cracking, indicates a different mass balance problem. The error within the engineered system appears to be similar to that in other compliance cases and is probably due to the same water vapor diffusion source problem. The mass balance in the remainder of the problem, however, shows a negative error which is larger than the error caused by the water vapor diffusion. In addition, the direction of the error is apparently not constant. The cause of the mass balance problem is not known. Because the engineered system contains all of the concrete and mass balance for the engineered system is not different in this case, the difference in mass balance is not attributed to the composite model being used for concrete water retention properties.

Figure P.23. Case 1.0 (central compliance case): Mass Balance as a Function of Time. Separate mass balances are tracked for the engineered system region (described above) and for the entire problem domain.

Figure P.24. Case 1.1 (delayed cracking): Mass Balance as a Function of Time. Separate mass balances are tracked for the engineered system region (described above) and for the entire problem domain.

Figure P.25. Case 1.2 (no HDPE flow path): Mass Balance as a Function of Time. Separate mass balances are tracked for the engineered system region (described above) and for the entire problem domain.

Figure P.26. Case 1.3 (composite model): Mass Balance as a Function of Time. Separate mass balances are tracked for the engineered system region (described above) and for the entire problem domain.

P.7 Section 4.1.3, Dose Analysis for Intruder Scenarios

To be complete, supplementary tables are included that show the inventory, dose factors, and percent of total dose for the full inventory analysis of the intruder dose calculations for both the drilling intrusion scenario and the post-drilling residential scenario. These tables are included here as Tables P.12-P.16.

Table P.12. Grout Inventory and Screening for Intruder Scenarios

Nuclide	32 Vault Campaign (7/93 Inventory)		
	Feed	Feed	Inventory (Ci)
	Conc. (uCi/L)	Conc. (Ci/m3)	Total Vol (L) 1.22E+08
H 3	5.07E+00	5.07E-03	6.19E+02
C 14	2.00E+00	2.00E-03	2.44E+02
CO 60	2.73E+01	2.73E-02	3.33E+03
NI 63	1.19E+02	1.19E-01	1.45E+04
SE 79	3.00E+00	3.00E-03	3.66E+02
SR 90+P	1.29E+04	1.29E+01	1.57E+06
ZR 95	1.73E+03	1.73E+00	2.11E+05
NB 95	1.78E+03	1.78E+00	2.17E+05
NB 94	1.30E-03	1.30E-06	1.59E-01
TC 99	5.17E+01	5.17E-02	6.31E+03
RU 103	1.29E+02	1.29E-01	1.57E+04
RU 106	1.84E+03	1.84E+00	2.24E+05
SN 113	1.78E+02	1.78E-01	2.17E+04
SB 125+P	5.41E+02	5.41E-01	6.60E+04
SN 126+P	9.10E+00	9.10E-03	1.11E+03
I 129	1.20E-01	1.20E-04	1.46E+01
CS 134	3.19E+02	3.19E-01	3.89E+04
CS 135	6.90E-01	6.90E-04	8.42E+01
CS 137	1.32E+05	1.32E+02	1.61E+07
CE 144+P	1.55E+03	1.55E+00	1.89E+05
EU 152	4.08E+00	4.08E-03	4.98E+02
EU 154	1.49E+02	1.49E-01	1.82E+04
EU 155	1.67E+02	1.67E-01	2.04E+04
RA 226+P	3.00E-06	3.00E-09	3.66E-04
U 238+P	7.94E-02	7.94E-05	9.69E+00
CM 244+P	5.28E-02	5.28E-05	6.44E+00
PU 241+P	8.90E+00	8.90E-03	1.09E+03
PU 239	2.59E+00	2.59E-03	3.16E+02
U 235+P	1.97E-02	1.97E-05	2.40E+00
PU 242	1.57E-05	1.57E-08	1.92E-03
PU 238	1.59E-01	1.59E-04	1.94E+01
AM 241	2.33E+01	2.33E-02	2.84E+03
CM 243+P	4.14E-02	4.14E-05	5.05E+00
NP 237+P	4.39E-01	4.39E-04	5.36E+01
TH 230+P	2.40E-03	2.40E-06	2.93E-01
U 234	3.37E-01	3.37E-04	4.11E+01

Table P.13. Driller Scenario Pathway Dose Factors (rem/year per Ci/m³ Grout)

		Time Post Disposal:			
		100 yr	300 yr	500 yr	1000 yr
H 3		1.40E-09	1.80E-14	2.30E-19	1.40E-31
C 14		1.30E-05	1.30E-05	1.30E-05	1.20E-05
CO 60		1.70E-06	5.70E-18	2.00E-29	0.00E+00
NI 63		3.90E-06	1.00E-06	2.50E-07	7.80E-09
SE 79		1.20E-04	1.20E-04	1.20E-04	1.20E-04
SR 90+P		3.80E-04	2.90E-06	2.23E-08	1.19E-13
ZR 95		0.00E+00	0.00E+00	0.00E+00	0.00E+00
NB 95		0.00E+00	0.00E+00	0.00E+00	0.00E+00
NB 94		5.70E-01	5.70E-01	5.70E-01	5.40E-01
TC 99		1.70E-05	1.70E-05	1.70E-05	1.70E-05
RU 103		0.00E+00	0.00E+00	0.00E+00	0.00E+00
RU 106		1.30E-31	0.00E+00	0.00E+00	0.00E+00
SN 113		0.00E+00	0.00E+00	0.00E+00	0.00E+00
SB 125+P		2.40E-12	4.71E-34	0.00E+00	0.00E+00
SN 126+P		7.96E-01	7.96E-01	7.96E-01	7.96E-01
I 129		1.90E-03	1.90E-03	1.90E-03	1.90E-03
CS 134		1.60E-15	0.00E+00	0.00E+00	0.00E+00
CS 135		9.70E-05	9.70E-05	9.70E-05	9.70E-05
CS 137		2.20E-02	2.20E-04	2.20E-06	2.20E-11
CE 144+P		4.03E-41	0.00E+00	0.00E+00	0.00E+00
EU 152		2.70E-03	1.00E-07	3.60E-12	3.00E-23
EU 154		1.70E-04	2.50E-11	3.40E-18	2.70E-35
EU 155		8.60E-09	6.00E-21	4.20E-33	0.00E+00
RA 226+P		7.59E-01	7.18E-01	6.59E-01	5.08E-01
U 238+P		1.29E-02	1.29E-02	1.29E-02	1.29E-02
CM 244+P		7.80E-04	1.40E-04	1.30E-04	1.30E-04
PU 241+P		1.61E-03	1.20E-03	8.40E-04	3.80E-04
PU 239		5.10E-02	5.10E-02	5.10E-02	5.10E-02
U 235+P		3.45E-02	3.64E-02	3.83E-02	4.30E-02
PU 242		4.80E-02	4.80E-02	4.80E-02	4.80E-02
PU 238		2.10E-02	4.30E-03	8.90E-04	1.70E-05
AM 241		4.60E-02	3.40E-02	2.50E-02	1.10E-02
CM 243+P		6.46E-03	1.12E-04	6.33E-05	5.89E-05
NP 237+P		1.62E-01	1.62E-01	1.62E-01	1.62E-01
TH 230+P		4.13E-02	1.04E-01	1.60E-01	2.89E-01
U 234		4.30E-03	4.30E-03	4.30E-03	4.30E-03

Table P.14. Driller Scenario Dose

Driller Scenario Dose (32 Vault Campaign)
(mrem/year)Driller Scenario Dose (32 Vault Campaign)
% of Total Dose

	Time Post Disposal:				Time Post Disposal:			
	100 yr	300 yr	500 yr	1000 yr	100 yr	300 yr	500 yr	1000 yr
Total	2.92E+03	3.73E+01	8.34E+00	7.72E+00	100.00	100.00	100.00	100.00
H 3	7.10E-09	9.13E-14	1.17E-18	7.10E-31	0.00	0.00	0.00	0.00
C 14	2.60E-05	2.60E-05	2.60E-05	2.40E-05	0.00	0.00	0.00	0.00
CO 60	4.64E-05	1.56E-16	5.46E-28	0.00E+00	0.00	0.00	0.00	0.00
NI 63	4.64E-04	1.19E-04	2.98E-05	9.28E-07	0.00	0.00	0.00	0.00
SE 79	3.60E-04	3.60E-04	3.60E-04	3.60E-04	0.00	0.00	0.00	0.00
SR 90+P	4.90E+00	3.74E-02	2.88E-04	1.54E-09	0.17	0.10	0.00	0.00
ZR 95	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
NB 94	7.41E-04	7.41E-04	7.41E-04	7.02E-04	0.00	0.00	0.01	0.01
TC 99	8.79E-04	8.79E-04	8.79E-04	8.79E-04	0.00	0.00	0.01	0.01
RU 103	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
RU 106	2.39E-28	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SN 113	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SB 125+P	1.30E-09	2.55E-31	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SN 126+P	7.25E+00	7.25E+00	7.25E+00	7.25E+00	0.25	19.41	86.93	93.92
I 129	2.28E-04	2.28E-04	2.28E-04	2.28E-04	0.00	0.00	0.00	0.00
CS 134	5.10E-13	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
CS 135	6.69E-05	6.69E-05	6.69E-05	6.69E-05	0.00	0.00	0.00	0.00
CS 137	2.90E+03	2.90E+01	2.90E-01	2.90E-06	99.54	77.78	3.48	0.00
CE 144+P	6.25E-38	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
EU 152	1.10E-02	4.08E-07	1.47E-11	1.22E-22	0.00	0.00	0.00	0.00
EU 154	2.53E-02	3.73E-09	5.07E-16	4.02E-33	0.00	0.00	0.00	0.00
EU 155	1.44E-06	1.00E-18	7.01E-31	0.00E+00	0.00	0.00	0.00	0.00
RA 226+P	2.28E-06	2.16E-06	1.98E-06	1.52E-06	0.00	0.00	0.00	0.00
U 238+P	1.02E-03	1.02E-03	1.02E-03	1.02E-03	0.00	0.00	0.01	0.01
CM 244+P	4.12E-05	7.41E-06	6.86E-06	6.86E-06	0.00	0.00	0.00	0.00
PU 241+P	1.43E-02	1.07E-02	7.48E-03	3.38E-03	0.00	0.03	0.09	0.04
PU 239	1.32E-01	1.32E-01	1.32E-01	1.32E-01	0.00	0.35	1.58	1.71
U 235+P	6.79E-04	7.17E-04	7.54E-04	8.47E-04	0.00	0.00	0.01	0.01
PU 242	7.54E-07	7.54E-07	7.54E-07	7.54E-07	0.00	0.00	0.00	0.00
PU 238	3.34E-03	6.84E-04	1.42E-04	2.70E-06	0.00	0.00	0.00	0.00
AM 241	1.07E+00	7.92E-01	5.83E-01	2.56E-01	0.04	2.12	6.99	3.32
CM 243+P	2.67E-04	4.63E-06	2.62E-06	2.44E-06	0.00	0.00	0.00	0.00
NI 237+P	7.11E-02	7.11E-02	7.11E-02	7.11E-02	0.00	0.19	0.85	0.92
TH 230+P	9.90E-05	2.50E-04	3.85E-04	6.94E-04	0.00	0.00	0.00	0.01
U 234	1.45E-03	1.45E-03	1.45E-03	1.45E-03	0.00	0.00	0.02	0.02

Table P.15. Post-Driller Garden Scenario Pathway Dose Factors (rem/year per Ci/m³ Grout)

		Time Post Disposal:			
		100 yr	300 yr	500 yr	1000 yr
H 3		4.30E-09	5.60E-14	7.00E-19	4.20E-31
C 14		4.30E-05	4.10E-05	4.10E-05	3.90E-05
CO 60		1.30E-05	4.70E-17	1.60E-28	0.00E+00
NI 63		1.40E-04	3.50E-05	8.80E-06	2.80E-07
SE 79		1.60E-03	1.60E-03	1.60E-03	1.60E-03
SR 90+P		4.77E-02	3.63E-04	2.80E-06	1.56E-11
ZR 95		0.00E+00	0.00E+00	0.00E+00	0.00E+00
NB 95		0.00E+00	0.00E+00	0.00E+00	0.00E+00
NB 94		4.70E+00	4.70E+00	4.70E+00	4.70E+00
TC 99		2.80E-02	2.80E-02	2.80E-02	2.80E-02
RU 103		0.00E+00	0.00E+00	0.00E+00	0.00E+00
RU 106		1.10E-30	0.00E+00	0.00E+00	0.00E+00
SN 113		0.00E+00	0.00E+00	0.00E+00	0.00E+00
SB 125+P		1.90E-11	3.70E-33	0.00E+00	0.00E+00
SN 126+P		6.45E+00	6.45E+00	6.45E+00	6.45E+00
I 129		3.80E-02	3.80E-02	3.80E-02	3.80E-02
CS 134		1.30E-14	0.00E+00	0.00E+00	0.00E+00
CS 135		4.30E-03	4.30E-03	4.30E-03	4.30E-03
CS 137		1.80E-01	1.80E-03	1.80E-05	1.80E-10
CE 144+P		3.39E-40	0.00E+00	0.00E+00	0.00E+00
EU 152		2.20E-02	8.10E-07	3.10E-11	2.60E-22
EU 154		1.40E-03	2.00E-10	2.90E-17	2.20E-34
EU 155		7.30E-08	5.00E-20	3.40E-32	0.00E+00
RA 226+P		6.03E+00	5.51E+00	5.06E+00	4.14E+00
U 238+P		2.23E-01	2.23E-01	2.23E-01	2.23E-01
CM 244+P		8.60E-03	1.50E-03	1.50E-03	1.40E-03
PU 241+P		1.81E-02	1.30E-02	9.40E-03	4.20E-03
PU 239		5.80E-01	5.80E-01	5.80E-01	5.70E-01
U 235+P		4.08E-01	4.46E-01	4.83E-01	5.78E-01
PU 242		5.50E-01	5.50E-01	5.40E-01	5.40E-01
PU 238		2.40E-01	4.90E-02	1.00E-02	2.00E-04
AM 241		5.20E-01	3.80E-01	2.70E-01	1.20E-01
CM 243+P		6.06E-02	1.19E-03	6.73E-04	6.69E-04
NP 237+P		1.87E+00	1.87E+00	1.87E+00	1.87E+00
TH 230+P		6.02E-01	1.14E+00	1.60E+00	2.57E+00
U 234		1.60E-01	1.60E-01	1.60E-01	1.60E-01

Table P.16. Post-Driller Scenario Dose

Post-Driller Scenario Dose (32 Vault Campaign)
(mrem/year)Post-Driller Scenario Dose (32 Vault Cam
% of Total Dose

	Time Post Disposal:				Time Post Disposal:			
	100 yr	300 yr	500 yr	1000 yr	100 yr	300 yr	500 yr	1000 yr
Total	2.45E+04	3.14E+02	7.14E+01	6.54E+01	100.00	100.00	100.00	100.00
H 3	2.18E-08	2.84E-13	3.55E-18	2.13E-30	0.00	0.00	0.00	0.00
C 14	8.60E-05	8.20E-05	8.20E-05	7.80E-05	0.00	0.00	0.00	0.00
CO 60	3.55E-04	1.28E-15	4.37E-27	0.00E+00	0.00	0.00	0.00	0.00
NI 63	1.67E-02	4.17E-03	1.05E-03	3.33E-05	0.00	0.00	0.00	0.00
SE 79	4.80E-03	4.80E-03	4.80E-03	4.80E-03	0.00	0.00	0.01	0.01
SR 90+P	6.15E+02	4.68E+00	3.61E-02	2.01E-07	2.52	1.49	0.05	0.00
ZR 95	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
NB 95	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
NB 94	6.11E-03	6.11E-03	6.11E-03	6.11E-03	0.00	0.00	0.01	0.01
TC 99	1.45E+00	1.45E+00	1.45E+00	1.45E+00	0.01	0.46	2.03	2.21
RU 103	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
RU 106	2.02E-27	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SN 113	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SB 125+P	1.03E-08	2.00E-30	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
SN 126+P	5.87E+01	5.87E+01	5.87E+01	5.87E+01	0.24	18.71	82.26	89.78
I 129	4.56E-03	4.56E-03	4.56E-03	4.56E-03	0.00	0.00	0.01	0.01
CS 134	4.15E-12	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
CS 135	2.97E-03	2.97E-03	2.97E-03	2.97E-03	0.00	0.00	0.00	0.00
CS 137	2.38E+04	2.38E+02	2.38E+00	2.38E-05	97.18	75.70	3.33	0.00
CE 144+P	5.26E-37	0.00E+00	0.00E+00	0.00E+00	0.00	0.00	0.00	0.00
EU 152	8.98E-02	3.30E-06	1.26E-10	1.06E-21	0.00	0.00	0.00	0.00
EU 154	2.09E-01	2.98E-08	4.32E-15	3.28E-32	0.00	0.00	0.00	0.00
EU 155	1.22E-05	8.35E-18	5.68E-30	0.00E+00	0.00	0.00	0.00	0.00
RA 226+P	1.81E-05	1.65E-05	1.52E-05	1.24E-05	0.00	0.00	0.00	0.00
U 238+P	1.77E-02	1.77E-02	1.77E-02	1.77E-02	0.00	0.01	0.02	0.03
CM 244+P	4.54E-04	7.94E-05	7.92E-05	7.39E-05	0.00	0.00	0.00	0.00
PU 241+P	1.61E-01	1.16E-01	8.37E-02	3.74E-02	0.00	0.04	0.12	0.06
PU 239	1.50E+00	1.50E+00	1.50E+00	1.48E+00	0.01	0.48	2.10	2.26
U 235+P	8.05E-03	8.78E-03	9.52E-03	1.14E-02	0.00	0.00	0.01	0.02
PU 242	8.64E-06	8.64E-06	8.48E-06	8.48E-06	0.00	0.00	0.00	0.00
PU 238	3.82E-02	7.79E-03	1.59E-03	3.18E-05	0.00	0.00	0.00	0.00
AM 241	1.21E+01	8.85E+00	6.29E+00	2.80E+00	0.05	2.82	8.81	4.28
CM 243+P	2.51E-03	4.92E-05	2.79E-05	2.77E-05	0.00	0.00	0.00	0.00
NP 237+P	8.21E-01	8.21E-01	8.21E-01	8.21E-01	0.00	0.26	1.15	1.26
TH 230+P	1.44E-03	2.72E-03	3.85E-03	6.16E-03	0.00	0.00	0.01	0.01
U 234	5.39E-02	5.39E-02	5.39E-02	5.39E-02	0.00	0.02	0.08	0.08

P.8 Section 4.1.4.4, Analysis of High Recharge

As described in Chapter 4, Case 1.4 analyzed a recharge rate of 5 cm/yr using a staged degradation model similar to that in the compliance cases. The moisture content contours resulting from a recharge rate of 5 cm/yr are shown in Figure P.27. The mass balance errors experienced in this case were greater than those experienced in cases with 0.1-cm/yr recharge. Figure P.28 shows a plot of the mass balance error for transport grout 1A (containing iodine-129) over time. The mass balance error is fairly small until 5,000 years and then increases rapidly. Separate mass balances are shown for the engineered system and the entire problem domain. As can be seen in Figure P.28, the source of the mass balance error is not within the engineered system. For comparison, see Figure P.23, which shows the mass balance error over time for the central compliance case. The mass balance error in the high recharge case appears to be due to a different phenomenon. The magnitude of the error is much greater than in the central compliance case, and the error appears to occur in the vadose zone rather than the engineered system. In addition, the error both increases and decreases at different times while the central compliance case error only increases.

Figure P.27. Case 1.4 (high recharge): Moisture Content Contours Within Vadose Zone at 10,000 Years for 5.0 cm/yr Recharge

Figure P.28. Mass Balance Error Over Time for Iodine-129 in Case 1.4

Figures P.29 and P.30 illustrate the amount of advective and diffusive transport from the engineered system in Case 1.4. As can be seen in the figures, the amount of transport occurring by advection is higher in this case as was the case with the 0.1-cm/yr recharge rate (see Figures P.15 and P.16).

Figure P.29. Release of Transport Group 1A (iodine-129) from the Engineered System by Advective and Diffusive Mechanisms

Figure P.30. Release of Transport Group 2A (technetium-99) from the Engineered System by Advective and Diffusive Mechanisms

P.9 Section 4.2.1.1, Central Sensitivity Case

P.9.1 Mass Balance Information

Figure P.31 shows the mass balance error experienced in Case 2.0 (central sensitivity case).

Figure P.31. Mass Balance Error for Case 2.0 (central sensitivity case). The central sensitivity case does not include a water source within the problem.

P.9.2 Water Flux in Cracks

In an attempt to increase understanding of the behavior of the central sensitivity case, the amount of water passing through the cracks in the barrier was monitored during the simulation. In the central sensitivity case, all cracks are modeled as 10-cm cracks filled with backfill soil. The flowrates into cracks (+) and out of cracks (-) are shown below for the 90,000-year period in which the barrier is intact. The flows are constant with time.

<u>Crack Location</u>	<u>L/yr/Vault</u>
Upper right vertical	+ 8.0
Upper left vertical	+ 5.9
Upper right horizontal	+16.0
Upper left horizontal	+ 6.0
Lower right horizontal	-18.0
Lower left horizontal	-18.1

P.10 Section 4.2.1.3, Sensitivity Cases for Engineered System

P.10.1 Grout

As noted in Chapter 4, the comparison between Cases 2.2D and 2.0 indicated that a two order-of-magnitude increase in diffusion coefficient produced a small counter intuitive increase in release. This was attributed to diffusion into the concrete where hydraulic conductivities are smaller than in the grout.

During this calculation, a boundary was drawn around the grout and cold grout along the inner boundary of the concrete on the top, bottom, and left side of the grout. On the right side of the problem, the boundary is located one node into the grout rather than at the grout/concrete interface. The flux out of this rectangular area from advection and diffusion was monitored over time in both Cases 2.2D and 2.0. The transport out of the region is 15% greater at 16,000 years for transport group 1A (iodine-129) with the higher diffusion coefficient. After 26,000 years, the integrated release from the grout is approximately equal. At this time in the central sensitivity case analysis, advection accounted for 31% of the cumulative contaminant transport across this boundary. In the case with a lower grout diffusion coefficient, advection accounted for 64% of the transport from the grout region. This information is consistent with the hypothesis that the higher diffusivity increased release by reducing the transport into the concrete where hydraulic conductivities (as well as diffusion coefficients) are lower. In the case of neptunium-237, the reduction in diffusion coefficient results in a small decrease in release. This is because the release is controlled by sorption in the grout while sorption is not modeled in the concrete. Therefore, for neptunium-237, transport into the concrete results in greater mobility rather than less.

P.10.2 RCRA Cover and Recharge Rate

Case 2.5B examined the impact of a recharge rate of 5 cm/yr. As outlined in Chapter 4, this produced approximately a factor of 10 increase in peak dose prior to barrier degradation and caused the arrival of contamination to occur much earlier. The flow into and out of the cracks was measured as it was in the central sensitivity case. The flow through cracks is provided below.

<u>Crack Location</u>	<u>Flow: L/yr/Vault</u>
Upper right vertical	+ 17.1
Upper left vertical	+ 15.0
Upper right horizontal	+292.8
Upper left horizontal	+ 68.1
Lower right horizontal	-207.0
Lower left horizontal	-186.0

As can be seen, the flows are roughly an order-of-magnitude greater than in the central sensitivity case. Thus, the higher recharge is increasing the flow through the cracks in the barrier. This is believed to be the key mechanism causing the higher level of releases. The high recharge also produces higher advection velocities in the soil, which dramatically shortens the arrival time.

The mass balance information in this case is shown in Figure P.32. As can be seen, the higher recharge increases the mass balance error relative to the central sensitivity case (compare Figure P.31). The reason for this is not known.

Figure P.32. Mass Balance Information for Case 2.5B, 5-cm/yr Recharge Sensitivity Case

P.10.3 Water Vapor Return

As noted in Chapter 4, the mass balance error was increased when a water source representing the diffusion of water vapor was added to the problem (Case 2.6A). Figure P.33 shows the mass balance error for Case 2.6A over time from 1,000 to 90,000 years. This figure can be compared to the mass balance results from the central sensitivity case shown previously in Figure P.31, which does not include a water source simulating water vapor return. Upon investigation, the increased mass balance error was determined to be due to a default in the code that caused the water source, being introduced to simulate water vapor diffusion, to enter the problem at the concentration currently present in the cell into which it was introduced. Because of this, the effect is most pronounced when the water vapor diffusion rates and concentrations in the cracks are highest. In addition, the problem always results in the addition of mass to the system and in this sense it is conservative. The source of the mass balance problem was not determined until after the compliance case simulations had been executed. Therefore, all compliance case simulations are also subject to this error. Mass balance errors for compliance cases was discussed in Section P.6.

Figure P.33. Mass Balance Error for Case 2.6A from 1,000 to 90,000 Years. Case 2.6A includes a water source in the upper cracks to represent water vapor diffusion.

P.11 Section 4.2.2, Sensitivity of the Unconfined Aquifer Analysis to Irrigated Agriculture

Four cases involving different recharge rates have been analyzed--a natural recharge, a 5-cm/yr increment over natural recharge, and two cases associated with irrigated agriculture. The first represents a post-Hanford aquifer with natural recharge. In this analysis the Grout Disposal Facility received 0.1-cm/yr infiltration through the barrier system. The other cases apply additional annual infiltration amounts of 5, 10.2, and 25.4 cm/yr. The 5-cm/yr case is the high recharge case which appears in the performance assessment. Cases involving 10.2- and 25.4-cm/yr are based on present trends in irrigated agriculture in Benton and Franklin counties. A rate of 10.2 cm/yr is the average recharge rate for a diverse pattern of crops. A rate of 25.4 cm/yr is associated with potatoes. When the Hanford Site becomes available for agriculture, the initial crop probably would be potatoes, which would do well in virgin soils. Crop diversification would take place after only a few years. Irrigated agriculture will probably occur as soon as the public is allowed unrestricted access.

The results of the analysis are summarized in Table P.17. Two blocks of information are presented. The first four rows report the analysis for a high pumping rate of 45 m³/d, the last four rows report that for a low pumping rate. Several related aspects of these analyses become clear. Greater recharge causes the aquifer thickness to increase. The flow field also shifts from easterly under the 0.1-cm/yr case, to

Table P.17. Summary of Well Intercept Factors for Infiltration and Pumping Rate Combinations

Case (cm/yr)	Aquifer Thickness (m)	Well Intercept (m)	Plume Width (m)	Average Gradient at Facility (dimensionless)	Groundwater or Well Discharge (m ³ /d)	Recharge from Facility (m ³ /d)	Well Intercept Factor
<u>High Pumping Rate (irrigated farm scenario)</u>							
0.1	21.1	144	255	4.76×10^{-4}	45	0.245	0.00308
5	25.1	160	416	3.9×10^{-4}	45	12.25	0.105
10.2	28.7	170	479	3.2×10^{-4}	45	25.0	0.197
25.4	36.9	32	479	5.28×10^{-4}	45	62.2	0.0924
<u>Low Pumping Rate</u>							
0.1	21.3	--	256	4.18×10^{-4}	24.6	0.245	0.010
5	25.2	--	416	3.1×10^{-4}	29.7	12.25	0.415
10.2	28.7	--	479	3.2×10^{-4}	35.3	25.0	0.708
25.4	36.9	--	479	5.28×10^{-4}	465.4	62.2	0.13366

northeasterly for the 5-cm/yr case, to northward for the 10.2-cm/yr case, and finally to the northwest for the 25.2-cm/yr case. This rotation of the flow field is a result of water which mounds on the plateau region of the site as it finds a way around Gable Mountain and to the Columbia River. As groundwater deepens in response to recharge, it simply finds it easier to move through the gap between Gable Mountain and Gable Butte and to the river, than to move directly east to the river. The plume width estimate is a direct result of the flow field rotation. As the field rotates from an easterly flow to a northerly flow, the longer axis of the site becomes perpendicular to the flow field. Clearly, the highest recharge case has a different response than the others. The depth of aquifer in this case implies that groundwater flow is occurring in the Hanford formation gravel sequence. This explains the greatly reduced well intercept width and the increased groundwater discharge.

Both analyses, negligible and 45-m³/d pumping rates, produce the highest well intercept factor for the case involving a diverse pattern of crops similar to those of Benton and Franklin counties. The lowest factors and greatest reduction in concentrations are a result of the lowest recharge, 0.1 cm/yr, which is associated with the permanent isolation barrier. This low recharge rate was employed in the majority of performance assessment cases.

P.12 References

- Allard, B., U. Olofsson, B. Torstenfelt, H. Kipatsi and K. Andersson. 1982. "Sorption of Actinides in Well-Defined Oxidation States on Geologic Media." *Scientific Basis for Nuclear Waste Management V*. Materials Research Society Vol. 11, Pittsburgh, Pennsylvania, p. 775-782.
- Ames, L. L., and R. J. Serne. 1991. *Compilation of Data to Estimate Groundwater Migration Potential for Constituents in Active Liquid Discharges at the Hanford Site*. PNL-7660, Pacific Northwest Laboratory, Richland, Washington.
- Benson, D. W. 1961. *Mineral Adsorption of Radionuclides in Reactor Effluent*. HW-69225, Hanford Works (General Electric), Richland, Washington.
- Bidoglio, G., A. Avogadro, and A. DePlano. 1985. "Influence of Redox Environments on the Geochemical Behavior of Radionuclides." *Scientific Basis for Nuclear Waste Management IX*. Materials Research Society Vol. 50, Pittsburgh, Pennsylvania, p. 709-716.
- Bird, R. B., W. E. Stewart, and E. N. Lightfoot. 1960. *Transport Phenomena*. John Wiley & Sons, Inc., New York.
- Bondietti, E. A. 1982. "Mobile Species of Pu, Am, Cm, Np and Tc in the Environment." *Environmental Migration of Long-Lived Radionuclides*. IAEA-SM-257/42, p. 81-96, International Atomic Energy, Vienna, Austria.
- Crank, J. 1975. *The Mathematics of Diffusion*. Oxford University Press, New York.
- Ewart, F. T., J. L. Smith-Briggs, H. P. Thomason, and S. J. Williams. 1992. "The Solubility of Actinides in a Cementitious Near-Field Environment." *Waste Management* 12:241-252.
- Freeze, R. A., and J. A. Cherry. 1979. *Groundwater*. Prentice-Hall, Englewood Cliffs, New Jersey.
- Girvin, D. C., L. L. Ames, A. P. Schwab, and J. E. McGarrah. 1991. "Neptunium Adsorption on Synthetic Amorphous Iron Oxyhydroxide." *J. of Colloid Interface Sci.* 141:67-78.
- Harr, M. E. 1962. *Groundwater and Seepage*. McGraw-Hill Book Company, New York.
- Hillel, D. 1982. *Introduction to Soil Physics*. Academic Press, New York.
- Höglund, S., L. Eliasson, B. Allard, K. Andersson, and B. Torstenfelt. 1985. "Sorption of Some Fission Products and Actinides in Concrete Systems." *Scientific Basis for Nuclear Waste Management IX*. Materials Research Society. Vol. 50, Pittsburgh, Pennsylvania, p. 683-690.

- Jury, W. A., W. R. Gardner, and W. H. Gardner. 1991. *Soil Physics*. John Wiley & Sons, New York.
- Keiling, Ch., and G. Marx. 1991. "Investigations into the Influence of Organic Complexing Agents on the Leaching Behavior and Mobility of Radionuclides Solidified in ILW Forms." *Radiochimica Acta*. 52/53:287-290.
- Kemper, W. D., and J. C. van Schaik. 1966. "Diffusion of Salts in Clay-Water Systems." *Soil Sc. Soc. Am. Proc.* 30:534-540.
- Klavetter, E. A., and R. R. Peters. 1986. *Estimation of Hydrologic Properties of An Unsaturated, Fractured Rock Mass*. SAND84-2642, Sandia National Laboratories, Albuquerque, New Mexico.
- Meyer, R. E., W. D. Arnold, and F. I. Case. 1985. Valence Effects on the Sorption of Nuclides on Rocks and Minerals II. NUREG/CR-4114, ORNL-6137, Oak Ridge National Laboratory, Oak Ridge, Tennessee.
- Mualem, Y. 1976. "A New Model for Predicting the Hydraulic Conductivity of Unsaturated Porous Media." *Water Resour. Res.* 12(3):513-522.
- Olsen, S. R., and W. D. Kemper. 1968. *Advances in Agronomy* 20:91-151.
- Porter, L. K., W. D. Kemper, R. D. Jackson, and B. C. Stewart. 1960. "Chloride Diffusion in Soils as Influenced by Moisture Content." *Soil Sc. Soc. Am. Proc.* 24:460-463.
- Rai, Dhanpat, and J. L. Ryan. 1985. "Neptunium (IV) Hydrous Oxide Solubility Under Reducing and Carbonate Conditions." *Inorg. Chem.* 24:247-251.
- Richards, L. A. 1931. "Capillary Conduction of Liquids in Porous Mediums." *Physics* 1:318-313.
- Routson, R. C., G. Jansen, and A. V. Robinson. 1975. *Sorption of ⁹⁹Tc, ²³⁷Np, and ²⁴¹Am on Two Subsoils From Differing Weathering Intensity Areas*. BNWL-1889, Pacific Northwest Laboratory, Richland, Washington.
- Routson, R. C., G. Jansen, and A. V. Robinson. 1976. "Sorption of ⁹⁹Tc, ²³⁷Np, and ²⁴¹Am on Two Subsoils from Differing Weathering Intensity Areas." *Health Phys.* 33:311-317.
- Serme, R. J., W. J. Martin, V. L. McGore, C. W. Lindenmeier, S. B. McLaurine, P.F.C. Martin and R. O. Lokken. 1989a. *Leach Tests on Grouts Made with Actual and Trace Metal-Spiked Synthetic Phosphate/Sulfate Waste*. PNL-7121, Pacific Northwest Laboratory, Richland, Washington.

Serne, R. J., W. J. Martin, R. O. Lokken, V. L. LeGore, C. W. Lindenmeier, and P. C. Martin. 1989b. *Leach and EP Toxicity Tests on Grouted Waste from Tank 106-AN*. PNL-6960, Pacific Northwest Laboratory, Richland, Washington.

Serne, R. J., and M. I. Wood. 1990. *Hanford Waste-Form Release and Sediment Interaction-A Status Report with Rationale and Recommendations for Additional Studies*. PNL-7297, Pacific Northwest Laboratory, Richland, Washington.

Serne, R. J., and M. I. Wood. 1990. *Hanford Waste-Form Release and Sediment Interaction*. PNL-7297, Pacific Northwest Laboratory, Richland, Washington.

Serne, R. J., R. O. Lokken, and L. J. Criscenti. 1992. "Characterization of Grouted Low-Level Waste to Support Performance Assessment." *Waste Management* 12:271-287.

Serne, R. J., C. W. Lindenmeier, J. L. Conca, V. L. LeGore, K. J. Cantrell, J. A. Campbell, J. E. Amonette, and M. I. Wood. 1993. *Solid Waste Leach Characteristics and Contaminant-Sediment Interactions*. PNL-draft, Pacific Northwest Laboratory, Richland, Washington.

Sheppard, J. C., J. A. Kittrick, and T. L. Hardt. 1976. *Determination of Distribution Ratios and Diffusion Coefficients of Neptunium, Americium, and Curium in Soil-Aquatic Environments*. RLO-2221-T-12-2 (WSU 76/13-33), Washington State University, Pullman, Washington.

Staunton, S., P. G. Clay, and L. V. C. Rees. 1990. "Diffusion of Neptunium (V) in Clays." *Radiochimica Acta*. 49:147-153.

Tallent, O. K., E. W. McDaniel, G. D. Del Cul, K. E. Dodson, and D. R. Trotter. 1988. "Immobilization of Technetium and Nitrate in Cement-Based Materials." *Mat. Res. Soc. Symp. Proc.* 12:23-32.

van Genuchten, M. Th. 1978. *Calculating the Unsaturated Hydraulic Conductivity with a New, Closed-Form Analytical Model*. Research Report 78-WR-08, Water Resources Program, Department of Civil Engineering, Princeton University, Princeton, New Jersey.

Appendix Q

Best Estimate Crack Predictions for the Grout Vault Engineered Barriers

Appendix Q

Best Estimate Crack Predictions for the Grout Vault Engineered Barriers

B. V. Winkel, Westinghouse Hanford Company

Q.1 Introduction

Precise crack predictions in asphalt and concrete are difficult even in controlled laboratory conditions. For the grout vault application, significant uncertainties exist in the stress magnitudes, even for the near-term loadings (settlement, thermal, shrinkage, soil/grout pressures, stress redistributions caused by asphalt creep). These load/stress uncertainties increase with time, particularly with regard to seismic events. Uncertainties in material property changes caused by aging and chemical reactions also increase with time.

Because the cracking estimates are used in flow/transport computer models, it was necessary to establish quantitative predictions. However, because of the uncertainties, it was not reasonable to attempt to numerically derive the quantitative crack estimates. A more reasonable approach was to base the estimates on judgment influenced by the limited available data. Because the uncertainties increase with time, the long-term crack estimates involve greater conjecture and larger spans of time were considered for the longer-term predictions provided in Section Q.3.

Although significant uncertainties exist in quantitative crack predictions, note that, in general, the grout vault design is relatively benign regarding crack potential. During normal loading, the general stress pattern is compressive (i.e. the loading imposed by the soil is inward on all outside surfaces of the vault). Because no structurally significant voids are inside the vault, there cannot be structural collapse or significant displacements and associated opening of cracks in the vault components. The buried, desert sand environment is also a significant factor in minimizing cracking. That is, a buried structure does not experience the freeze/thaw, wet/dry, or hot/cold cycling which is experienced by a surface structure. The aging effects of air/oxygen, sunlight, and drying shrinkage are also reduced.

Therefore, cracking should be minimal and cracks would tend to remain closed. The one potential exception to this statement is with the asphalt walls. Between the asphalt and concrete walls is one inch of thermal insulation board, which may compress and/or disintegrate with time. Should this occur, the voided space may result in a downward flow or "slumping" of the asphalt walls and the asphalt wall could separate from the asphalt roof.

Q.2 Procedures for Establishing Crack Estimates

Given the uncertainties in the crack predictions, the ideal procedure is to perform a probabilistic evaluation. However, a quantitative probabilistic analysis is not feasible because there is insufficient data on the uncertainty distributions for the significant parameters. Another alternative for dealing with significant uncertainties is to base the crack predictions on highly pessimistic assumptions for all parameters involved. However, the resulting combination of worst case assumptions could produce an extremely conservative estimate with little meaning. The grout vault performance assessment analysts' consensus was that the most meaningful approach would be to establish a "best estimate" for each of the potential cracking mechanisms.

The first step in the crack prediction effort was to review the existing literature relative to potential crack mechanisms in concrete and asphalt. For concrete, a relatively comprehensive list of crack mechanisms is available in ACI 224.1R (ACI 1984). Based on ACI 224.1R and other literature on concrete and asphalt cracking, it was decided to develop a grout vault "relative significance" number for each of the potential cracking mechanisms. A significance factor for each mechanism was found by multiplying a relative "probability of occurrence" times a "consequence factor" using a scale of 1 to 5. The resulting "significance factor" product potentially ranges from 1 to 25. This effort is summarized in Attachment 1. The results are shown in Table Q.1. The significance factors were used in the crack predictions provided in Section Q.3 below.

The development of the significance factors for concrete cracking, summarized in Attachment 1, was patterned after a Failure Modes and Effects Analysis (FMEA) tool used for evaluating potential failures in military and aerospace hardware. [Refer to DOD (1980).] An FMEA uses relative probability of occurrence and failure consequences to focus on design improvements which will increase reliability in service. It is a relatively simple, qualitative alternative to a full-fledged probabilistic evaluation. The results given in Table Q.1 provide information to identify the more important crack mechanisms for the grout vault application.

In addition to the ACI 224.1R committee report, several other documents about concrete cracking and durability were reviewed. [Refer to Clifton (1989), Walton (1990), Hookham (1991).] The grout vault stress reports were also reviewed (KEH 1991, Winkel 1992). These documents also influenced the cracking estimates described in the next section.

The asphalt cracking predictions were influenced by the following efforts: 1) asphalt pavement literature review, 2) review of grout vault asphalt design documentation, and 3) discussions with asphalt aging experts. The contribution of the asphalt paving experience to the grout vault is limited because the grout vault application significantly departs from a typical pavement design (i.e., loading, thickness, environment, mix design, and design life).

Table Q.1. Relative Significance of Potential Cracking Mechanisms
(Listed in order of significance, highest first)

Component	Cracking Mechanism	Significance Factor
Concrete Vault	Long-Term Seismic Loading	16
	Long-Term Rebar Corrosion	16
	Roof Cracking Between Roof Planks	16
	Wall/Floor Construction Joints	15
	Short-Term Drying Shrinkage	9
	Short-Term Thermal Stress	8
	Chemical Degradation Mechanisms	8
	Fresh Concrete Settlement in Floor	6
	Externally Applied Loads	4
	Long-Term Drying Shrinkage	3
	Short-Term Rebar Corrosion	3
	Poor Construction Practices	3
	Design Detailing Errors	3
	Short-Term Seismic Loading	3
	Fresh Concrete Plastic Shrinkage	2
	Weathering	2
Asphalt Barrier	Thermal Board Disintegration	15
	Long-Term Seismic Stresses	8
	Thermal Stresses	6
	Construction Joint Cracks	5
	Shrinkage Cracking	4
	Crack Enlargement from Biodegradation	4
	Fatigue Cracking	3
	Short-Term Seismic Stresses	3

Concerning design documentation, a significant material property testing effort was conducted for the grout vault asphalt mix design (Vallerga 1992). The Vallerga report recommended using a 1% tensile strain criteria to avoid cracking. As indicated in Section Q.1, under normal loading the general stress state is compressive. This means that if the 1% strain criteria is exceeded, it would be local in nature and not project through the wall, for the short term. The one possible exception to this statement is the wall/roof intersection region discussed in Section Q.1.

For the long term, cracking can be influenced by asphalt aging/hardening. If the asphalt becomes embrittled, surface cracks may extend through the wall thickness during a seismic event. Based on consulting with asphalt aging experts, the consensus was that for the thick, relatively impermeable grout vault asphalt walls, the aging, and associated cracking, should be a surface phenomena.

Q.3 Best Estimate Crack Predictions

From Table Q.1, the more significant contributors to concrete cracking for the grout vault are 1) seismic-induced cracking, 2) rebar corrosion, 3) roof cracking between roof planks, and 4) built-in cracks at construction joints. To simplify the concrete cracking predictions, it was assumed that the concrete cracking would be dominated by these four mechanisms. This assumption was influenced by the existence of an asphalt liner on the inside surface of the concrete walls. The sealing effect of this liner should compensate for the minor cracking mechanisms.

Using the procedures discussed in Section Q.2, the best estimate crack predictions given in Table Q.2 were obtained. The rationale for these predictions is summarized in the remainder of this section. Note that the crack descriptions are divided into time periods of increasing length. For flow modeling purposes, it can be assumed that the described cracking occurs in the middle of the period or, more conservatively, in the beginning of the period.

Q.3.1 0- to 100-Year Time Period

As shown in Table Q.2, limited cracking is predicted for the first 100 years. The only expected significant cracking is between the planks in the roof. The roof planks are 4-ft wide precast panels. Following placement, the joints between planks are grouted and a thin, lightly reinforced cap is placed over the entire roof. As overburden weight is added from the roof asphalt and cover soil, it is likely that through-wall cracks will form at the roof plank joints.

Some minor cracking in the concrete is expected from drying shrinkage and/or thermal stresses in the first 100 years. If any of these cracks should extend through the wall, they should remain sealed because of the presence of the asphalt liner. Rebar corrosion should not be significant in the first 100 years because cathodic protection exists for the rebar, if needed. For the asphalt, some cracking may occur in the upper corners due to wall slumping, but it is not expected to extend through the wall because of the compressive character of the stress and the ductile nature of the asphalt.

Q.3.2 100- to 1,000-Year Time Period

For the 100- to 1,000-year time period, the only through-wall cracks predicted for the asphalt are at the top corners. This position is based primarily on the assumption that the asphalt core remains ductile, preventing permanent through-wall cracks. For the concrete, it is assumed that the metal water stops in the construction joints have lost their ability to seal due to corrosion. Some rebar corrosion is predicted, but it is assumed that there is insufficient corrosion and seismic activity to expect significant through-wall cracking.

Concerning rebar corrosion, many quantitative corrosion predictor models in the literature exist. [Refer to Walton (1990).] All of these models are limited to chloride ion attack because, historically,

Table Q.2. Best Estimate Crack Predictions

Time Period (Years)	Component	Through-Wall Crack Descriptions
0 - 100	Asphalt Barrier	<ul style="list-style-type: none"> Initiation of surface cracks in upper corners caused by asphalt wall "slumping," but no through-wall cracks. 0.5-mm-wide cracks between each 4-ft (122-cm) roof plank. Wall and floor cracks, if any, will be sealed by asphalt liner.
	Concrete Vault	
100 - 1,000	Asphalt Barrier	<ul style="list-style-type: none"> 5-mm through-wall cracks develop in the wall/roof intersection region, caused by additional wall slumping and seismic activity. Surface hardening results in some surface cracking, but through-wall cracks exist only in the upper corners.
	Concrete Vault	
1,000 - 10 ⁴	Asphalt Barrier	<ul style="list-style-type: none"> Additional hardening, biodegradation, and cracking at the surface, but sufficient soft core prevents crack extension through the wall, except at the upper corners. Upper corner through-wall cracks remain at 5-mm size.
	Concrete Vault	
10 ⁴ - 10 ⁵	Asphalt Barrier	<ul style="list-style-type: none"> Additional surface degradation (hardening, biodegradation) results in some surface cracks extending through the wall. Assume 1-mm cracks every 1 m. Upper corner through-wall cracks remain at 5-mm size.
	Concrete Vault

this has been the source of rebar corrosion (e.g. de-icing salts on bridge decks). The application of these models to the grout vault environment (i.e., chemistry) is questionable. On the positive side, corrosion is less likely for low water cement ratio mix designs and high pH environments, both of which are true for the grout vaults. However, it is difficult to prove that significant rebar corrosion will not eventually occur and it was therefore assumed that corrosion-induced surface cracks develop during the 100- to 1,000-year time period.

Q.3.3 1,000- to 10,000-Year Time Period

Based on the assumption that the asphalt hardening is a surface phenomena, through-wall cracking in the asphalt was assumed to be limited to the upper corners for the 1,000- to 10,000-year time period. This prediction was also influenced by the results of seismic analyses of the grout vault asphalt (Winkel 1992), which indicated relatively low seismic stresses in the asphalt. For the concrete vault, it was assumed that seismic activity results in a widening of the existing cracks as well as through-wall extension of 10% of the corrosion-induced surface cracks.

Q.3.4 10,000- to 100,000-Year Time Period

It was assumed for the 10,000- to 100,000-year time period that biodegradation and surface cracking results in hardening progressing through the thickness of the asphalt barrier. It was further assumed that during seismic events through-wall cracks would occur throughout the asphalt barrier. Cracking of the concrete was assumed to follow the pattern of the previous time period (i.e., widening of existing cracks and the introduction of new cracks).

Q.4 References

ACI. 1984. *Causes, Evaluation, and Repair of Cracks in Concrete Structures*. ACI 224.1R, American Concrete Institute Committee Report, ACI Manual of Concrete Practice, Vol. 3.

Clifton, J. R. and L. I. Knab. 1989. *Service Life of Concrete*. NUREG/CR-5466, NISTIR 89-4086.

DoD. 1980. *Procedures for Performing a Failure Mode, Effects and Criticality Analysis*. MIL-STD-1629A, Department of Defense, November 24, 1980.

Hookham, C. J. 1991. *Structural Aging Assessment Methodology for Concrete Structures in Nuclear Power Plants*. ORNL/NRC/LTR-90/17, March 1991.

KEH. 1991. *Engineering Report, Vault Design, Work Order ER9089*. Kaiser Engineers Hanford, January 1991.

Vallerga, B. A. 1992. *Characterization Study of Asphalt Concrete Barrier Material for Radioactive Waste Vaults*. B. A. Vallerga, Inc., March 1992.

Walton, J. C. 1990. *Models for Estimation of Service Life of Concrete Barriers in Low-Level Radioactive Waste Disposal*. NUREG/CR-5542, September 1990.

Winkel, B. V. 1992. *Grout Vault Asphalt Barrier Seismic Adequacy, Preliminary Report*. Westinghouse Hanford Co., Facility Stress Analysis, April 21, 1992.

Attachment 1.

Evaluation of Concrete Cracking Mechanisms

Summary of Evaluation of Potential Cracking Mechanisms in the Grout Vault Structures

Material	Cracking Mechanism	Probability of Occurrence	Consequence Factor	Significance Factor	Comments
Vault Concrete	Plastic Shrinkage (Fresh Concrete)	1	2	2	Only occurs on hot dry days when improper curing practices are employed. Generally occurs in horizontal slabs, which, for the grout vault, would be the floor of the vault. If such a condition developed in the vault floor, it is highly probable that it would be detected and corrected.
	Fresh Concrete Settlement	3	2	6	Generally occurs immediately above rebar in flat slabs when improper placing procedures are used. Some problems with this mechanism occurred in the initial vaults.
	Short-Term Drying Shrinkage (Hardened Concrete)	3	3	9	Cracks are generally shallow, immediately above the rebar. Generally caused by surface drying faster than the interior, which could occur in the vaults before grout fill. Cracks generally are relatively tight and limited to the surface.
	Long-Term Drying Shrinkage	1	3	3	Through-wall cracks occur only if full section is in tension (e.g., wall shrinkage restricted by grout). In the long term, humid environment of the buried vaults, drying shrinkage should be minimal.
Vault Concrete	Thermal Stress (Short Term)	4	2	8	Based on conservative thermal stress analysis of grout fill.
	Thermal Stress (Long Term)	1	2	2	Some long-term chemical degradation of the concrete is likely. However, it is also likely that the consequences will be minimized because the reaction products are expansive and will tend to seal cracks as they develop. Some seismically-induced crack opening and resealing is expected.
	Concrete Chemical Reactions	4	2	8	Three types of weathering in ACI 224.1R (freeze/thaw, wet/dry, heating/cooling). As buried structures, the vaults should not experience significant weathering.
	Weathering	1	2	2	Short-term rebar corrosion is unlikely because 1) cathodic protection is available, 2) short-term pH is high, 3) low permeability concrete is used, 4) relatively low chlorides with limited free moisture is present, and 5) vault asphalt liner separates grout from the concrete walls.
	Rebar Corrosion (Short Term)	1	3	3	

Summary of Evaluation of Potential Cracking Mechanisms in the Grout Vault Structures (contd)

Material	Cracking Mechanism	Probability of Occurrence	Consequence Factor	Significance Factor	Comments
Vault Concrete	Rebar Corrosion (Long Term)	4	4	16	Over a long time period, depassivation of the steel reinforcement is likely due to a gradual lowering of the pH (carbonation and/or leaching). Grout chemistry degradation of the rebar cover concrete also could contribute to an eventual initiation of corrosion.
	Poor Construction Practices	1	3	3	ACI 224.1R lists several poor construction practices which can cause cracking. The grout vault construction is relatively well controlled and should not have significant problems of this type. If construction-related cracking does occur, it is likely to be discovered and corrected.
	Construction Overloads	1	2	2	Concrete is susceptible to cracking during construction because the young concrete has not achieved full strength. However, the carefully controlled grout vault construction should prevent any construction overloads.
	Design Detailing Errors	1	3	3	Since the grout vault design has been subjected to significant review, design/detailing errors are not likely.
Vault Concrete	Externally Applied Loads, Dead	2	2	4	Dead weight/soil pressure loadings maximum stress predictions are below the minimum cracking strength.
	Weight/Soil Pressure	1	3	3	Short-term probability of a seismic event is low. Consequences are low for nondegraded structure.
	Seismic Loading (Short Term)	4	4	16	Long-term probability of a seismic event is much higher. Long-term consequences are high due to degradation from other mechanisms. This would include both the extension of existing cracks and the introduction of new cracks.
	Seismic Loading (Long Term)	4	4	16	Nonreinforced joints between roof planks are filled with field grout followed with a relatively thin layer of concrete topping over the entire roof. Some cracking will likely occur at these locations because of overburden loading.
Asphalt Diffusion Barrier	Roof Cracking Between Precast Planks	4	4	16	Construction joints are designed into the walls and the floor. Metal water stops seal the joints initially but the long-term sealing ability is questionable.
	Construction Joints	5	3	15	Shrinkage may occur from loss of volatiles and/or chemical reactions. The absence of information in the literature on this mechanism leaves the impression that this is not a significant mechanism.

Summary of Evaluation of Potential Cracking Mechanisms in the Grout Vault Structures (contd)

Material	Cracking Mechanism	Probability of Occurrence	Consequence Factor	Significance Factor	Comments
Asphalt Diffusion Barrier	Thermal Stress	2	3	6	Asphaltic concrete has a relatively high thermal expansion coefficient, resulting in a higher potential for significant thermal stresses. However, thermal stresses are highest in the first few years following grout fill, when the asphalt should be relatively ductile, reducing the probability of thermal cracking.
	Fatigue Cracking	1	3	3	Fatigue cracking is observed in highway pavements due to the high degree of cyclic loading. Other than some limited cycling due to seismic loading, the vault stresses are not cyclic.
	Seismic Stresses (Short Term)	1	3	3	The short-term seismic mechanism should not be significant because the probability of significant seismic loading is low and in the short term, the asphalt is relatively ductile.
	Seismic Stresses (Long Term)	2	4	8	Based on estimates from asphalt aging experts, the vault asphalt hardening should be a surface phenomena. A seismic event could extend or initiate cracks in the hardened surface and accelerate the depth of hardening.
	Construction Joints	1	5	5	Cold pour/construction joints in the asphalt barrier are potential planes of weakness, but the healing nature of the fresh asphalt is expected to make this mechanism insignificant. A high consequence factor was assumed because many cold pour joints are in the asphalt walls.
Asphalt Diffusion Barrier	Thermal Board Disintegration	3	5	15	Thermal board disintegration could contribute to asphalt wall "slumping" which could produce cracks in the wall/roof joint area. The best estimate disintegration of the thermal board is a minimal, slow process based on wood disintegration in the anticipated environment (asphalt coated, low moisture, low air availability).
	Biodegradation-Induced Crack Enlargement	2	2	4	Biodegradation at cracks in highway pavements has been noted in the literature. It is postulated that the increased surface area exposed by cracks could accelerate the biodegradation and increase the effective size of the cracks.

Appendix R

Compilation of Responses to Requests for Further Information Made by the Peer Review Panel

February 1994 - October 1994

Appendix R

Compilation of Responses to Requests for Further Information Made by the Peer Review Panel

This appendix compiles the Peer Review Panel's (PRP) requests for further information about the analyses presented in this performance assessment, and the authors' responses to those requests. The requests and responses are organized as outlined here:

pages R.3 - R.152:

Letter from Charles T. Kincaid to Elmer L. Wilhite (letter dated March 25, 1994) transmitting information requested by the Peer Review Panel during their February 1994 review.

TOPICS: 1) Provide a corrected copy of Table 1-4 with the full exponent field printed in the "total mean" column.^(a)

2) Provide a roadmap tracing inventory values from their origin in Appendix E (Hendrickson and Conner 1993) to final values shown in Table 2.4 of the performance assessment.

3) Provide additional information regarding the dose assessment for Tc-99 and I-129, i.e., provide literature references, numerical value, and rationale for the selection for soil-water partition coefficients, concentration and biotransfer factors, and dose-conversion factors.

pages R.153 - R.155:

Letter from Elmer L. Wilhite to George F. Williamson (letter dated April 26, 1994) requesting additional information for PRP review of the Hanford grout performance assessment.

TOPIC: Provide the panel with information to allow the assessment of the dose impact for the Central Compliance case for the groundwater protection and garden scenarios, as well as the farm scenario, with failure of the asphalt barrier, concrete vault, and grout at a time earlier than presented in the performance assessment.

(a) This comment refers to the waste feed projection document upon which the performance assessment analyses were based. Revision 0 of that document (WHC-SD-WM-TI-528, Hendrickson and Conner 1993) is included in this volume as Appendix E. That document was subsequently revised to incorporate minor corrections to the inventory projections. The revised version, WHC-SD-WM-TI-528 Rev. 1, is included in this appendix.

- pages R.156 - R.182: Letter and attachments from Charles T. Kincaid to George F. Williamson (letter dated June 16, 1994) transmitting additional information requested by Elmer L. Wilhite.
TOPIC: Further information for two cases that exhibit aspects of early release resulting from a lack of integrity within the asphalt, concrete, and grout engineered components.
- pages R.183 - R.186: Letter from Charles T. Kincaid to Elmer L. Wilhite (letter dated July 14, 1994) transmitting supplementary information related to the June 16, 1994, transmittal.
TOPIC: Clarification of the dose estimated for Ru/Rh-106.
- pages R.187 - R.190: Letter from Charles T. Kincaid to George F. Williamson (letter dated September 29, 1994) transmitting information requested by Stanley Neuder of the DOE Peer Review Panel.
TOPIC: Effects from earlier breakdown of the barrier systems (the central compliance case versus the time-shifted central compliance case); potential for adjacent plumes affecting concentrations in the well located 100-m downgradient of the grout disposal facility.
- pages R.191 - R.197 Letter from Elmer L. Wilhite to J. A. Turi (letter dated October 4, 1994) transmitting the Peer Review Panel recommendations regarding the grout performance assessment.
TOPIC: "Panel finding is that the analyses presented are *technically adequate* but that the approach taken is *not consistent with the development and application of PA models around the DOE complex*." The letter also outlines recommendations for revising the grout performance assessment.

Pacific Northwest Laboratories
 Battelle Boulevard
 P.O. Box 999
 Richland, Washington 99352
 Telephone (509) 376-8324

March 25, 1994

Dr. Elmer L. Wilhite
 % Mr. Robert Curl
 765 Lindsay Blvd (TSB)
 Idaho Falls, Idaho 83415-2420

Dear Dr. Wilhite:

Ref: Responses to Information Requested by the Peer Review Panel during the February 9-10, 1994 meeting in Dallas, Texas.

Enclosed please find materials submitted in response to the three topics on which additional information was requested. The three topics and our submitted materials are listed below:

- 1) Provide a corrected copy of Table 1-4 with the full exponent field printed in the "total mean" column.

Response: The revision to Table 1-4 is provided in a complete Revision No. 1 copy of the waste feed projection document (Hendrickson and Conner 1994). The tables and text of this document are completely linked such that changes in tables flow into successive tables and text references to table entries. In order to incorporate minor changes to the inventory projection that have come to light since the Revision No. 0 document (Hendrickson and Conner 1993) was published and incorporated into the Hanford Grout PA, it was necessary to enter the changed table fields and "regenerate" the document. The roadmap provided in response to the next request describes the minor changes to the inventory and their negligible influence on results reported in the PA.

- 2) Provide a roadmap tracing inventory values from their origin in Appendix E (Hendrickson and Conner 1993) to final values shown in Table 2.4 of the PA (Kincaid et al. 1993).

Response: The requested roadmap, an inventory data flow chart, and a markup copy of Table 2.4 (Kincaid et al. 1993) are enclosed. The roadmap text and associated diagram will enable the reader to better understand the flow of information. Information presented focuses on the top three contributors to estimates of long-term groundwater pathway exposure and dose, (i.e., Tc-99, I-129, and Np-237), and how data from waste sampling and analysis, the DOE complex integrated database, and ORIGEN2 (reactor fuel burnup) estimates were all considered in determining the base case and sensitivity cases for waste feed projections.

Minor errors discovered in the spreadsheet equations since publication of Hendrickson and Conner (1993) have been corrected in the Revision No. 1 copy of the waste feed projection (Hendrickson and Conner 1994). These spreadsheet errors and their corrections are described in the roadmap, and it is noted they have no adverse effect on the results of the PA.

The roadmap text also clarifies how and why blanks in the data were interpreted differently for DSSF family and pretreatment wastes. As this

Dr. Elmer L. Wilhite.
March 25, 1994
Page 2

topic was further explored with respect to pretreatment wastes, the potential influence on the total feed projection arising from blanks for Tc-99 in the CC waste stream data was studied. Insufficient information exists to estimate the Tc-99 inventory in CC wastes. However, application of the only currently available CC supernatant analysis from a single tank suggests a potentially significant increase in total Tc-99 inventory could occur when CC wastes are fully characterized and sent to the grout facility for disposal. Such an increase should be bounded by the sensitivity case derived from total production. Note, the total inventory of radionuclides addressed in the Hanford Grout PA remains unchanged and is reported in Table 2.4 of the PA (Kincaid et al. 1993). A commitment is made in the PA to review and revise the PA as required when changes to the inventory occur. Such changes would be based on either new measurements or revised estimation methods.

A markup copy of Table 2.4 from the PA (Kincaid et al. 1993) is included to clearly show the influence on the total feed concentrations of changes shown in the tables of Hendrickson and Conner (1994). This markup does not constitute a revision to the inventory analyzed for and reported in the PA. It is included to demonstrate that the spreadsheet errors and their corrections have no adverse effect on the inventory and results reported in the PA.

3) Provide additional information regarding the dose assessment for Tc-99 and I-129, i.e., provide literature references, numerical value, and rationale for the selection for soil-water partition coefficients, concentration and biotransfer factors, and dose-conversion factors.

Response: The requested supplemental information is provided for the partition (adsorption) coefficients, concentration and biotransfer factors, and the dose-conversion factors. Because these parameters appear as default settings in the GENII code for Hanford Site applications, they were not included as variables in the sensitivity analysis. Qualitative information on the sensitivity of dose projections to partition coefficients and dose-conversion factors is provided in the attachment. References are provided to documents which support the selection of concentration and bioaccumulation factors.

If the enclosed information has not adequately addressed the three topics for which supplemental information was requested during the Dallas meeting, please call me on (509) 376-8324, or FAX requests for supplemental information to me at 509-376-5368.

Very truly yours,

C. T. Kincaid, Staff Scientist
Near Surface Hydrologic Processes Technical Group
EARTH & ENVIRONMENTAL SCIENCES CENTER

CTK/tar

Enclosures

THE INVENTORY ROADMAP

INTRODUCTION

The chemical and low-level radioactive waste (LLW) inventory presented as Table 2.4 in the Hanford grout performance assessment (PA) document (Kincaid et al., October 1993; WHC-SD-WM-EE-004, Rev.0) derives from waste feed projections prepared by Hendrickson and Conner (January 1993; WHC-SD-WM-TI-528, Rev.0) which appears as Appendix E in the PA.

Double-shell tank (DST) wastes are divided into two general types of waste; 1) double-shell slurry feed (DSSF) family wastes and 2) pretreatment wastes. The composition of DSSF family and pretreatment wastes was estimated based on results of direct sampling and waste analyses, and process flowsheet information. A volume-weighted average of concentration in these two waste streams is the basis for the first estimate of feed concentration to the grouted waste form. This first estimate appears as Table 4 in Hendrickson and Conner (1993).

To determine whether this first estimate should be altered, and to define the range of the inventory for sensitivity analyses regarding some especially important isotopes, the Table 4 waste-analyses based inventory estimates were compared to the integrated database inventory maintained for the DOE complex, and to estimates of fission product production based on ORIGEN2 code simulations. This roadmap emphasizes Tc-99, I-129, and Np-237 due to their importance to long-term dose through the groundwater dose pathway as determined through an analysis of the full inventory. However, special estimates were developed for twelve (12) radionuclides for which the uncertainty in inventory was great enough to potentially affect PA results in one or more exposure scenario. The radionuclides selected for special estimates were C-14, Se-79, Nb-94, Tc-99, Sn-126, I-129, Cs-135, Ra-226, Th-230, Np-237, U-238, and Am-241. Results from the special estimates of inventory for these 12 isotopes are shown in Table 8 in Hendrickson and Conner (1993). The feed concentrations of Table 4 (Hendrickson and Conner 1993), as modified by the special estimates (i.e., Table 8 and Section 4 of Hendrickson and Conner 1993), are presented as Table 2.4 in the PA (Kincaid et al. 1993).

Tables 1-2 and 1-4 in the appendix of Hendrickson and Conner (1993) summarize feed concentration information on the DSSF family and pretreatment wastes scheduled for LLW disposal and bring the radionuclide inventories to a common decay date of October 1, 1993. Note, other tables in the appendix of Hendrickson and Conner, which report analytical data on individual tanks or waste streams, present radionuclide concentrations and inventory data for a variety of decay dates. The "Total Family" column from Table 1-2 and the "Total Mean" column from Table 1-4 are brought forward as columns 2 and 3 in Table 4 of Hendrickson and Conner (1993).

All other tables that appear in the appendix of Hendrickson and Conner (1993) present analytical data and analyses (averages) on individual tanks or waste streams of the DSSF family wastes, and this information is compiled in Table 1-2. All data presented on pretreatment waste streams in Table 1-4 were drawn from Lowe (1991). A chart is attached which shows the flow of data from the appendices of Hendrickson and Conner (1993) to Table 2.4 of the PA (Kincaid et al. 1993).

The remainder of this inventory roadmap provides comment on aspects of the compilation for Tables 1-2, 1-4, 4, and 8 from the waste feed projections (Hendrickson and Conner 1993) and Table 2.4 from the PA (Kincaid et al. 1993). Arranged in this order, the flow of information can be shown from data sources to integrated PA inventory. Remarks on two miscellaneous topics, (i.e.,

detection limit reporting and waste volumes), follow the comment sections for individual tables. Results are provided of a brief review we have conducted regarding the potential for Tc-99 and I-129 to be found in CC wastes. A summary concludes the roadmap.

DSSF FAMILY WASTES AND TABLE 1-2

"Key to the handling of data within the first two categories (data based upon direct sampling or evaporative processing of current and future wastes which will not be pretreated) is the knowledge that the sources for these wastes are common. Each of these wastes are the combined product of the miscellaneous low-level liquid wastes of Hanford's 100, 200, 300, and 400 Areas. Because the waste sources are similar they constitute a family which is herein described as the "DSSF Family" of wastes. ... This familial relationship ... is not perfect but allows data gaps to be bridged and the mean concentration of an analyte to be reasonably estimated in the absence of some data. As an example, if potassium concentrations are described for four of six tanks in the family, the mean of all six tanks is represented as the mean of the four tanks for which data (are) provided" (Hendrickson and Conner, 1993, pg 3-1).

Thus, general knowledge of the similarity of wastes in the DSSF family enable one to calculate the average concentration of the chemical or radionuclide in the DSSF family by omitting the volume of waste associated with the blank from the average calculation. Information from blank table entries is simply omitted from both the numerator and denominator of the averaging operator (Equation 3-1, page 3-4, Hendrickson and Conner, 1993), i.e.,

$$Mean_i = \frac{\sum_{j=1}^n [C]_{ij} \times Volume_j}{\sum_{j=1}^n Volume_j} \quad [Eq.3.1]$$

Thus, the average concentration is calculated using only non-zero concentrations and associated waste volumes, but it is applied to the entire estimated volume of DSSF family wastes. This method of forming the average is applied in a straight-forward manner in Table 1-2 and in all but one of the tables feeding information to Table 1-2.

The single departure from this averaging method occurred when a special estimate of the contents of Tank 241-AP-106 was incorporated in the estimate for dilute wastes. The inventory of three tanks for which analytical data exist was combined with that of AP-106 which was estimated separately (Hendrickson and Welsh, 1992). The analytical mean (i.e., column 6 of Table 1-1) is the result of analytical results reported for tanks 103-AP (col 2), 106-AW (col 3), and 102-AW (col 4). The rule governing blanks in data fields was applied when data from these three tanks were used to calculate the analytical mean. The analytical mean was weighted by the volume of all three tanks when it was subsequently volume averaged with the estimated contents of tank 106-AP (Col 5) to form the overall-dilute mean (col 8).

Another aspect of Table 1-1 deserving comment involves the standard deviations reported opposite "analytical" and "overall dilute" columns. The standard deviation values reported are not volume weighted, and therefore, are not

related to the volume-weighted mean values reported in adjacent columns. Rather, they are generated by viewing the entries for individual tanks as individual measurements of equal weight, and they should be viewed as a simple measure of the variability of measured values about their linear average.

Since publication of Hendrickson and Conner in January 1993 (Rev.0) some minor errors in the spreadsheet equations were discovered. They are corrected in the updated copy of the document (Rev.1, attached) and result in minor changes in Tables 1-1, 1-2, and 4. The radioactive isotopes affected in Table 1-1 are Se-79, Eu-154, U-234, U-235, U-238, Pu-239/240, and Am-241. In Table 1-2 the affected isotopes are H-3, Se-79, Cs-134, Eu-154, U-234, U-235, U-238, Pu-239/240, and Am-241. Changes in the "Total Family" column of Table 1-2 (which is forwarded to Table 4) result in lower values than in the Rev.0 document or in only minor changes to the third significant digit. Therefore, these errors and their corrections have no adverse impact on the dose projections in the PA.

PRETREATMENT WASTE SOURCES AND TABLE 1-4

"... the conduct of pretreatment operations and the data provided do not allow handling of data in the manner of the DSSF family. (These) data (are) recognized to be incomplete, as not all analytes were followed through the flowsheets and because the differing nature of the sources do not allow one to make generalizations based on (the) similarity of waste sources. In addition, proposed treatment regimes differ for the various waste streams. Thus, in (developing a total inventory for) expected waste streams from these operations, the mean of all waste streams was calculated as the weighted average of all streams. If no data (were) provided for an analyte in a stream, the weight assigned was zero while the volume of the stream remained a part of the calculation. This may introduce some non-conservative estimates for some analytes; however, it is believed that most analytes of potential concern in large streams are reported and form the basis of this family's estimate" (Hendrickson and Conner, 1993, pg 3-1).

Thus, general knowledge of the dissimilar nature of the pretreatment wastes prevents one from using the weighted average of measured values to define the average of the waste stream. Blanks are now significant in a different way. Blanks are treated as zero or relatively low and inconsequential values in a given waste stream. The volume of the waste stream is weighted with a zero in the numerator of Eq 3-1, and included in the total volume accumulated in the denominator. The degree to which the waste stream inventory actually departs from a zero or negligible value represents a non-conservatism in the "total mean" determined for the pretreated wastes (Table 1-4) and brought forward into Table 4.

Because of their significance to projected dose through the groundwater pathway, three radioactive isotopes are of key interest; Tc-99, I-129, and Np-237. Potentially significant blanks appear in the rows of Table 1-4 associated with each of these isotopes. For example, blanks appear in the column associated with "CC waste" for each of these key isotopes. The significance of this is that CC wastes makeup approximately 64% (by volume) of grout feed originating as pretreated wastes, and consequently, approximately 32% (by volume) of the total feed to grout. (This issue will be revisited in this inventory roadmap in the section on Tc-99 and I-129 content in CC wastes.) Other blanks that appear in the inventories of Tc-99 and I-129 are associated with the second-pass through an ion-exchange process (i.e., neutralized current acid waste (NCAW), Stream 13). It was reasonably assumed that all Tc-99 and I-129 appeared in the first-pass waste stream from the ion-exchange process (i.e., NCAW, Stream 12). With respect to Np-237, there was only one entry in the table; that for Plutonium Finishing Plant (PFP) wastes. It was based entirely on measured levels in sludge because no measurements

were available for supernatant. Clearly, a relatively limited characterization database was available for those wastes designated for pretreatment.

Note that the revision copy of Table 1-4 contains the full exponent field in the "Total Mean" column. This corrects the "printing" error found in Table 1-4 of Hendrickson and Conner (1993) which appeared as Appendix E in the PA.

TABLE 4

Table 4 in Hendrickson and Conner (1993) brings together the DSSF family waste composition (i.e., the "Total Family" column from Table 1-2) and the pretreatment waste composition (i.e., the "Total Mean" column from Table 1-4). The volumes of these waste streams are shown at the end of the table as 6.08×10^7 and 6.12×10^7 liters respectively and make up 49.84% and 50.16% of the waste volume going to grout. When a blank appears in Table 4, the value from the other waste stream (for which a waste concentration exists) is assumed to apply to the total feed stream coming to grout. Thus, blanks in the table are interpreted as a concentration equivalent to that in the other column to avoid dilution due to a lack of information.

As noted at the close of the section entitled "DSSF Family Wastes and Table 1-2" inventory values for select radioactive isotopes were altered in the Rev.1 copy of Table 1-2 and these changes also appear in the Rev.1 copy of Table 4. Affected isotopes are H-3, Se-79, Cs-134, Eu-154, U-234, U-235, and U-238. In all cases the Rev.1 "Total Feed" concentration values either decreased from the Rev.0 values or involved a change in the third significant digit. Therefore, the spreadsheet errors and their corrections have no adverse affect on the results in the PA.

TABLE 8

In part, because of the limited characterization database available for pretreatment wastes, information available from (1) estimates of fission product production from the ORIGEN2 code, (2) the Hanford Defence Waste Environmental Impact Statement (HDW-EIS) (DOE 1987), and (3) the DOE integrated data base (IDB) was applied to provide a comparative evaluation of the inventory of critical isotopes. Estimates resulting from the evaluation of twelve (12) isotopes including Tc-99, I-129, and Np-237 are summarized by Hendrickson and Conner in Table 8. These special estimates were used to modify the base case inventory estimate or to define sensitivity analyses for the inventory. Estimates completed for the key isotopes, (i.e., Tc-99, I-129, and Np-237), are summarized below.

Technetium Estimation: Four methods or sources of information were available as estimates of the Tc-99. They were described in Subsection 4.6 of Hendrickson and Conner. Based on these four sources the following table can be generated;

<u>Method or Source</u>	<u>Tc-99 Concentration ($\mu\text{Ci/L}$)</u>	<u>Tc-99 Inventory (Ci)</u>
Waste Analysis (Table 4)	51.7	6,311
Integrated Data Base (IDB)	109	13,300
Production (ORIGEN2)	176.9	21,581
HDW-EIS (DOE 1987)	(156) ^a	19,000

^(a) equivalent concentration is based on volume of grout feed, 1.22×10^8 liters.

"In view of the proximity of Table 4 estimates (based upon waste analyses) to production and (IDB) estimates, the recommended base case for waste evaluation is that described in Table 4 of 51.7 $\mu\text{Ci/L}$. Sensitivity cases for evaluation would be those of production at 176.9 $\mu\text{Ci/L}$ and of IDB inventory at 109 $\mu\text{Ci/L}$ " (Hendrickson and Conner 1993, Subsection 4.6 ⁹⁹Technetium Estimation).

¹²⁹Iodine Estimation: Four methods or sources of information were also available as estimates for I-129. They were described in Subsection 4.4 of Hendrickson and Conner. Based on these four sources the following table can be generated;

<u>Method or Source</u>	<u>I-129 Concentration ($\mu\text{Ci/L}$)</u>	<u>I-129 Inventory (Ci)</u>
Waste Analysis (Table 4)	0.122	14.8
IDB	(0.00217) ^a	0.265
Production (ORIGEN2)	0.381	46.4
HDW-EIS (DOE 1987)	0.279	34

(^a) equivalent concentration is based on volume of grout feed, 1.22×10^6 liters.

Although it would have been beneficial to demonstrate that the IDB estimate limits I-129 disposal in grouted wastes, the magnitude of effort required to substantiate the IDB was beyond the scope of the Hanford Grout Technology Program. Furthermore, the IDB inventory value is two orders-of-magnitude below the waste-analysis estimate, and therefore, is immediately called into question. The waste analysis results (0.122 $\mu\text{Ci/L}$) were adopted as the base case and the HDW-EIS (0.279 $\mu\text{Ci/L}$) and production/ORIGEN2 (0.381 $\mu\text{Ci/L}$) estimates were adopted as sensitivity cases. These sensitivity cases represent a doubling and tripling of the base-case inventory estimate. A sensitivity case based on the IDB data would represent more than an order-of-magnitude decrease in I-129 inventory and is not recommended (paraphrased from Hendrickson and Conner 1993, Subsection 4.4 ¹²⁹Iodine Estimation).

²³⁷Neptunium Estimation: Four methods or sources of information were available as estimates for Np-237. They were described in Subsection 4.2.2 of Hendrickson and Conner. Based on these four sources the following table can be generated;

<u>Method or Source</u>	<u>Np-237 Concentration ($\mu\text{Ci/L}$)</u>	<u>Np-237 Inventory (Ci)</u>
Waste Analysis (Table 4)	0.44	53.6
IDB	0.37	45.1
Production (ORIGEN2)	0.56	68.9
HDW-EIS (DOE 1987)	0.279	34

"It is recommended that the base case of waste evaluation, when such is applied in long-term dose assessments, remain that provided in Table 4. Two sensitivity cases, one of lower activity and one higher, may be supported with the IDB estimate and the expected production estimate respectively. As each of these sensitivity cases is within a factor of two of the recommended base case, it is noted that inaccuracies or differences in transport modeling may obviate any long-term dose sensitivity due to such a minor variance in waste activity" (Hendrickson and Conner, 1993, Subsection 4.2.2 Revision of ²³⁷Neptunium Estimates).

TABLE 2.4

Inventory values reported in Table 2.4 of the PA are simply taken from Table 4 with values in Table 8 resulting from the special estimation for critical isotopes (Section 4 of Hendrickson and Conner 1993, Rev.0 and Rev.1) superseding values in Table 4. A markup copy of Table 2.4 based on the Hendrickson and Conner (1994, Rev.1) is attached. Listed below are only those radioactive isotopes impacted by the update;

Waste Component Radionuclide	Rev.0 Total Feed: Concentration ($\mu\text{Ci/L}$)	Rev.1 Total Feed: Concentration ($\mu\text{Ci/L}$)
^3H	5.07	5.12
^{129}I	0.12	0.122
^{154}Eu	1.49×10^2	9.73×10^1
^{226}Ra	3.0×10^{-6}	4.0×10^{-6}
^{230}Th	2.4×10^{-3}	3.1×10^{-3}
^{234}U	3.37×10^{-1}	4.45×10^{-2}
^{235}U	1.97×10^{-2}	2.71×10^{-3}
^{238}U	7.94×10^{-2}	1.0×10^{-2}

With respect to the radionuclide inventory, the only isotopes exhibiting a potentially significant increase were Ra-226 (33%) and Th-230 (29%). The analysis presented in the PA for radon release from the grout disposal facility, which is based on a relatively simple conceptual model, showed a peak radon-222 release of about 8 pCi/m³s. Due to the reduction in U-234 inventory the peak Ra-222 impact is reduced. The performance objective for radon release at the surface is 20 pCi/m³s. Thus, changes that have come to the attention of the PA staff in the total feed inventory estimate since the PA was drafted and issued to the PRP have not significantly altered the inventory, and do not require additional analysis.

MISCELLANEOUS TOPICS

Detection Limit Reporting: When the concentration of a constituent is below the detection limit of the measurement method, the analytical value typically reported is the detection limit value. Such data are labeled as a "less-than" value. Where such data were used by Hendrickson and Conner (1993), they were acted upon and weighted with other analyses as if they were real values. This application of limiting values as real values is inherently conservative, and was considered a reasonable way to use the data directly in the development of a generalized inventory estimate. In keeping with the application of "less-than" values as real values, the tables used here to summarize the total feed inventory to grout, (i.e., Tables 1-2, 1-4, 4, and 8 of waste feed projections, and Table 2.4 of the PA), do not carry the "less-than" indicators.

Waste Volumes: Volumes associated with the waste tanks and waste streams contributing to the LLW were taken from Hanlon (1992), Koreski and Strode (1992), and Lowe (1991) and reported in Table 1 of Hendrickson and Conner (1993). These reports contained the most recent estimates of waste volumes to

be fed to grout when Hendrickson and Conner compiled their report. Note, there are differences between some of the volumes shown in Table 1 and those reported in the tables for individual tanks or waste streams in the appendix of the Hendrickson and Conner document. The tank and waste stream data in the appendix reflect the volume of the wastes present when the characterization effort was conducted. However, volumes reported in Table 1 were the most current estimates of waste volumes to be delivered to grout, and therefore, superseded the volumes shown in the appendix. Hence, available waste analyses were used to estimate the composition of each waste stream, and these compositions were then applied to the forecast volume of each waste stream coming to grout.

COMMENT ON CC WASTES REGARDING ⁹⁹TECHNETIUM AND ¹²⁹IODINE

While creating this roadmap, it became apparent that the absence of data for Tc-99 and I-129 in the pretreatment data for complexant concentrate (CC) wastes, resulted in CC waste contributions being neglected in the estimation of these key isotopes in the total feed composition. The base-case inventory for Np-237 (0.44 $\mu\text{Ci/L}$) lies very close to both the IDB (0.37 $\mu\text{Ci/L}$) and production (0.56 $\mu\text{Ci/L}$) estimates, so it is not at issue.

CC wastes are distinguished from other wastes because they contain soluble organic complexants. While a number of organic compounds were used in Hanford Site chemical processing facilities, most of the organic compounds in the waste were introduced as chelating agents during strontium recovery processing at B Plant (DOE 1987, Subsection A.1.5 "Double-Shell Tank Waste Characterization", pg A.9-A.10).

Through a review of PUREX and B Plant processes published in ERDA (1975), and from conversations with WHC staff familiar with B Plant operation, it has been determined that CC wastes derived from currently generated PUREX sludges and from alkaline sludges recovered from tanks which were then acidified for Sr removal. Cs was first precipitated by contacting the waste stream with phosphotungstic acid. Then Sr was recovered by processing the acid waste through a four-column solvent extraction system. Complexants were added in the first extraction column, and CC waste was the waste stream from the first column. The complexants caused Sr along with some Ce and rare earth elements to be extracted to the organic phase and acted to prevent aluminum, iron, and manganese from being extracted with Sr. Highly mobile radioactive isotopes such as Tc-99 and I-129 can be expected to be in the waste stream from the first column. Thus, from a review of the processes involved, it is likely that Tc-99 and I-129 will be found in CC wastes.

The original waste stream is dominated by alkaline sludges recovered from tanks, rather than by PUREX sludges from current acid wastes (CAW). Because these sludges were not characterized for Tc-99 and I-129 content prior to Sr removal in B Plant, and because we have not yet determined volume changes associated with the Sr extraction process and subsequent concentration of (and/or additions to) the waste, it is not possible to estimate from a knowledge of the source, the Tc-99 and I-129 contents of CC waste.

Oscarson and Tusler (1993) produced a summary of all waste analyses completed to date on samples recovered from the double-shell tanks at the Hanford Site. They report the following for the 5 tanks containing either CC waste or dilute complexed (DC) waste (note: these two waste types are lumped together as CC waste in pretreatment wastes):

Tank 241-AN-102 (currently all CC waste): A single Tc-99 measurement for supernate of 309 $\mu\text{Ci/L}$, and a less-than value for solids were reported in August 1991. No measurement was reported for I-129.

Tank 241-AN-107 (currently all CC waste): No measurements are reported

for Tc-99 or I-129.

Tank 241-AY-101 (currently all DC waste): A single Tc-99 measurement of 19.6 $\mu\text{Ci/L}$ was reported in March 1987 for an unspecified sample type (supernate or sludge or crust), and a less-than value was shown for I-129 for the same sample.

Tank 241-SY-101 (May 1991 - 49.6% CC and 50.4% double shell slurry wastes; about the same in May 1986): Tc-99 measurements of 91, 195, and 209 $\mu\text{Ci/L}$ were reported for slurry in May 1986, and values of 1.33 and 0.000884 $\mu\text{Ci/L}$ were reported for the crust in May 1991. No measurement was reported for supernate. Two less-than values for I-129 are reported for the crust samples. No I-129 measurements were reported for supernate or slurry.

Tank 241-SY-103 (currently ~63% double shell slurry and ~37% CC wastes): No measurements are reported for Tc-99 or I-129.

As is apparent, few data are available on Tc-99 levels in CC wastes, and even less is known about I-129 levels. While more data are becoming available on the CC wastes in SY-101 (i.e., this tank has been the focus of attention for 2 years because of periodic hydrogen gas buildup and release), insufficient data exist at this time to characterize the Tc-99 and I-129 levels in CC wastes with any confidence.

To get a feeling for the potential significance of Tc-99 levels in the CC waste stream, let's examine the influence of a hypothetical uniform level of Tc-99 in the tanks for all CC waste. Because it is the tank with our only supernate measurement, we'll assume AN-102 is typical and use its supernate Tc-99 concentration of 309 $\mu\text{Ci/L}$, as well as its supernate Na content and volume to determine a feed concentration for 5M Na CC waste. Note, 5M Na was the Na level stipulated by the pretreatment program for delivering feed to the grout facility. Tank 241-AN-102 contains 4.16×10^6 L (1100 kgal) of supernate containing 1.0×10^9 g of Na; the supernate is 10.4M Na (Oscarson and Tusler 1993, pg D-7)¹. Reducing to a 5M Na level implies dilution of the waste stream, and radionuclide concentrations would drop accordingly by the ratio $[5/(10.4)]$ or 0.481 (assuming a diluent free of Tc-99 and I-129). The hypothetical Tc-99 concentration of 309 $\mu\text{Ci/L}$ would drop to

$$[309 \mu\text{Ci/L} \times 0.481] = 149 \mu\text{Ci/L}$$

in the 5M Na CC waste fed to the grout facility. Because the CC waste makes up 3.9×10^7 L of the overall 1.22×10^8 L of grout feed, the incremental increase in Tc-99 concentration in the grout feed would be

$$[(149 \mu\text{Ci/L}) \times (3.9 \times 10^7 \text{ L}) / (1.22 \times 10^8 \text{ L})] = 47.6 \mu\text{Ci/L}$$

and the total feed concentration would be

$$[51.7 + 47.6] = 99.3 \mu\text{Ci/L}.$$

Thus, if Tc-99 levels in the CC waste tanks were uniformly 309 $\mu\text{Ci/L}$, the

¹ The Tc-99 concentration datum is associated with an August 1991 sample while the Na concentration datum is associated with a February 1985 sample. The volume of CC wastes in Tank 241-AN-102 in February 1985 was 1124 kgal (1100 kgal of supernate) and in August 1991 it was 1097 kgal. The fill record indicates a gradual decline in volume from 1985 to 1991. Thus, it is assumed the Na concentration and supernate volume from 1985 can be used with the Tc-99 concentration from 1991 to estimate the required dilution of the tank contents to reach a 5M Na waste stream.

impact would be to nearly double the estimated total feed concentration. However, this doubled value remains within the production based sensitivity case analyzed and presented in the PA.

SUMMARY

A roadmap is provided which details the presentation and manipulation of inventory within the baseline inventory document (Hendrickson and Conner 1993 and Appendix E of the PA), and the incorporation of inventory tables from Hendrickson and Conner into the main text of the PA (Kincaid et al, 1993).

The Hanford Grout PA was written to and is governed by the total inventory analyzed and presented in Table 2.4 of the October 1993 edition. This total inventory (Table 2.4) was based on an interpretation of available measurements and estimates of the radionuclides present. Future changes to the inventory, measured or estimated, would need to be carefully evaluated. As stated in the PA (Kincaid, et al. 1993, pg 2.51), "The total inventory for each radionuclide in Table 2.4 is considered the maximum inventory that can be disposed of in grout under this performance assessment. If the inventory to be disposed exceeds the Table 2.4 values, the impact on the performance assessment will be evaluated and the performance assessment revised as required."

Subsequent to the publication of Hendrickson and Conner (1993) some minor errors were discovered in the spreadsheet equations. The influence of these errors on inventory (Tables 1-2 and 4 of Hendrickson and Conner 1993; Table 2.4 of Kincaid et al. 1993) are described in the preceding text. These spreadsheet errors and their corrections have no adverse effect on the results of the PA.

Creation of the roadmap has focused attention on the CC waste stream and implications for the total feed composition arising from possible levels of both Tc-99 and I-129 in that pretreatment waste stream. However, insufficient data exist to quantify the levels of Tc-99 and especially I-129 in that waste stream. A sample calculation based on a hypothetical uniform Tc-99 level of 309 $\mu\text{Ci/L}$ in CC waste stored in tanks revealed that Tc-99 concentration in the total feed to grout could nearly double. This amount of change in Tc-99 is currently bounded by the sensitivity cases included in the PA. Sensitivity cases for Tc-99 and I-129 were based on the production (ORIGEN2) inventory, the DOE integrated data base inventory, and the inventory previously reported in the HDW-EIS (DOE 1987). Therefore, it is believed the potential impacts of elevated levels of Tc-99 and I-129 in CC wastes are bounded by the inventory sensitivity analyses presented in the PA.

REFERENCES

DOE. 1987. Final Environmental Impact Statement, Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington. DOE/EIS-0113, 5 Volumes. United States Department of Energy, Washington, D.C.

ERDA. 1975. Final Environmental Statement, Waste Management Operations, Hanford Reservation, Richland, Washington. ERDA 1528, 2 Volumes. United States Energy Research and Development Administration, Washington, D.C.

Hanlon, B.M. 1992. "Tank Farm Surveillance and Waste Status Summary Report for February 1992," WHC-EP-0182-47, May 1992.

Hendrickson, D.W. and J.M. Conner. 1993. Grout Treatment Facility Waste Feed Projections. WHC-SD-WM-TI-528, Rev.0. Westinghouse Hanford Company, Richland, Washington.

Hendrickson, D.W. and T.L. Welsh. (January 30) 1992. "Tank 241-AP-106

Sampling and Characterization Plan," WHC-SD-WM-TP-117, Rev.0. Westinghouse Hanford Company, Richland, Washington.

Kincaid, C.T., et al. (October) 1993. Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford. WHC-SD-WM-EE-004, Rev.0, 2 Volumes. Westinghouse Hanford Company, Richland, Washington.

Koreski, G.M. and J.N. Strode. 1992. "Operational Waste Volume Projections," WHC-SD-WM-ER-029, Rev.16, October 28, 1992.

Lowe, S.S. 1991. "Preliminary Material Balances for Pretreatment of NCAW, NCRW, PRP, and CC Wastes." WHC-SD-WM-TI-492, Rev.0, Westinghouse Hanford Company, Richland, Washington.

Oscarson, E.E. and L.A. Tusler. (July 30) 1993. Radionuclide and Chemical Inventories for the Double-Shell Tanks. WHC-SD-WM-TI-543, Rev.1. Westinghouse Hanford Company, Richland, Washington.

INVENTORY DATA FLOW CHART

In the following chart, the flow of information from one table to the next is indicated by the vertical arrow. For example, Table 3-3 data flows vertically to Table 3-5, which flows to Table 4-3, which flows to Table 1-2, which flows to Table 4, which flows to Table 2.4. As is apparent from the flow chart, only Table 1-4 in the appendix of Hendrickson and Conner (1993) deals with pretreatment waste; all other tables in the appendix of the waste feed projection document deal with the DSSF family wastes. Only Table 2.4 appears in the main text of the PA (Kincaid et al. 1993). All other tables listed below appear in the waste feed projection document (Hendrickson and Conner, 1993) which appears as Appendix E of the PA. References to source publications are indicated in parantheses.

Table 2.4 Waste Components Analyzed in This Performance Assessment

- ↑ Table 8 Special Estimates of Critical Isotopes
- ↑ Table 4 Grout Treatment Facility Waste Projection
 - ↑ Table 1-4 Pretreatment Waste Summary (1)
 - ↑ Table 1-2 DSSF Family Waste Summary
 - ↑ Table 1-1 Dilute Waste Summary (2)
 - ↑ Table 2-4 241-AP-103 Analysis Summary
 - ↑ Table 2-1 241-AP-103 Validated Analysis Data (3)
 - ↑ Table 2-5 241-AW-106 Analysis Summary
 - ↑ Table 2-2 241-AW-106 Validated Analysis Data (3)
 - ↑ Table 2-6 241-AW-102 Analysis Summary
 - ↑ Table 2-3 241-AW-102 Validated Analysis Data (3)
 - ↑ Table 1-3 DSSF Family Radiolytic Heat Loading (4,5)
 - ↑ Table 2-7 Future Dilute DSSF Waste Summary
 - ↑ Table 1-1 Dilute Waste Summary
 - ↑ Table 4-1 Concentrated Waste Summary Data - 101AW, 103AN (6,7)
 - ↑ Table 4-2 Concentrated Waste Summary Data - 105AP, 106AN (7,8,9)
 - ↑ Table 4-3 Concentrated Waste Summary Data - 104AN, 105AN
 - ↑ Table 3-1 Evaporator Campaign 84-3 Analysis Data (10)
 - ↑ Table 3-4 Evaporator Campaign 84-5 Analysis Summary
 - ↑ Table 3-2 Evaporator Campaign 84-5 Analysis Data (11)
 - ↑ Table 3-5 Evaporator Campaign 85-3 Analysis Summary
 - ↑ Table 3-3 Evaporator Campaign 85-3 Analysis Data (12)

REFERENCES (from Hendrickson and Conner 1993)

- (1) Lowe, S.S. 1991. "Preliminary Material Balances for Pretreatment of NCAW, NCRW, PFP, and CC Wastes." WHC-SD-WM-TI-492, Rev.0, September 10, 1991.
- (2) Hendrickson, D.W. and T.L. Welsh. 1992a. "Tank 241-AP-106 Sampling and Characterization Plan." WHC-SD-WM-TP-117, Rev.0, January 30, 1992.

- (3) O'Rourke, J.F. 1992. "Process Control Plan for 242-A Evaporator Campaign 93-1. WHC-SD-WM-PCP-008, Rev.0. November 24, 1992.
- (4) Hendrickson, D.W. 1991a. "Radiolytic Heat Loading Calculation Methods for the Hanford Grout Disposal Facility." WHC-SD-WM-TI-455, Rev.0, January 2, 1991.
- (5) Hendrickson, D.W. 1991b. "Grout Treatment Facility Waste Feed Acceptance Criteria." WHC-SD-WM-RD-019, Rev.1, October 18, 1991.
- (6) Welsh, T.L. 1991b. "Tank 241-AW-101 Characterization Results." WHC-SD-WM-TRP-055, Rev.0, December 19, 1991.
- (7) Hendrickson, D.W. 1990. "Methods and Data for Use in Determining Source Terms for the Grout Disposal Program. SD-WM-TI-355, Rev.1, March 22, 1990.
- (8) Hendrickson, D.W. and T.L. Welsh. 1992b. "Tank 241-AP-105 Sampling and Characterization Plan." WHC-SD-WM-TP-130, Rev.0, April 16, 1992.
- (9) Welsh, T.L. 1991a. "Tank 241-AN-106 Characterization Results." WHC-SD-CP-TP-065, Rev.0, March 8, 1991.
- (10) Certa, P.J. 1985. "242-A Evaporator/Crystallizer FY 84 Campaign Run 84-3 Post Run Document." SD-WM-PE-018, April 30, 1985.
- (11) Gratny, E.G. 1985. "242-A Evaporator/Crystallizer FY 84 Campaign Run 84-5 Post Run Document." SD-WM-PE-022, September 4, 1985.
- (12) Pontious, N.L. 1986. "242-A Evaporator/Crystallizer FY 1985 Campaign 85-3 Post Run Document." SD-WM-PE-023, Rev.0, February 24, 1986.

ATTACHMENT No. 3

MARKUP OF TABLE 2.4, PG 2.52-2.55, KINCAID ET AL. (1993)

Table 2.4. Waste Components Analyzed in This Performance Assessment

Waste Component: Chemicals	Total Feed: Concentration (M) ^(a)	Total Inventory: (kg) ^(b)	Molecular Weight (g/mol)
Ag	6.48×10^{-5}	8.53×10^2	107.868
Al	4.48×10^{-1}	1.47×10^6	26.9815
As	1.99×10^{-4}	1.82×10^3	74.9216
B	3.37×10^{-3}	4.44×10^3	10.81
Ba	8.22×10^{-5}	1.38×10^3	137.33
Be	1.78×10^{-3}	1.96×10^3	9.0122
Bi	3.13×10^{-4}	7.98×10^3	208.98
Ca	3.87×10^{-3} 4.16×10^{-3}	1.89×10^4 2.03×10^4	40.08
Cd	1.12×10^{-4}	1.54×10^3	112.41
Ce	1.44×10^{-4}	2.46×10^3	140.12
Cr	1.18×10^{-2}	7.49×10^4	51.996
Cu	2.79×10^{-4}	2.16×10^3	63.546
Fe	1.01×10^{-2}	6.38×10^4	55.847
Hg	5.49×10^{-6}	1.34×10^2	200.59
K	2.00×10^{-1}	9.54×10^5	39.0983
La	1.15×10^{-4}	1.95×10^3	138.906
Li	6.31×10^{-5}	5.77×10^1	6.941
Mg	2.83×10^{-3}	8.39×10^3	24.305
Mn	3.66×10^{-3}	2.45×10^4	54.938
Mo	6.40×10^{-4}	7.49×10^3	95.94
Na	5.50	1.54×10^7	22.9898
Nd	1.20×10^{-4}	2.11×10^3	144.24
Ni	1.26×10^{-3}	9.02×10^3	58.70
P	4.98×10^{-2}	1.38×10^5	30.9738
Pb	3.27×10^{-4}	8.27×10^3	207.2
Sb	6.36×10^{-4}	1.02×10^4	121.75
Se	3.95×10^{-4}	3.31×10^3	78.96
Si	6.38×10^{-3}	2.08×10^4	28.0855

WHC-SD-WM-EE-004, Rev. 0

Table 2.4. (contd)

Waste Component: Chemicals	Total Feed: Concentration (M) ^(a)	Total Inventory: (kg) ^(a)	Molecular Weight (g/mol)
Ta	1.36×10^{-3}	3.00×10^2	180.948
Ti	9.55×10^{-3}	5.58×10^2	47.90
V	3.14×10^{-4}	1.95×10^3	50.9415
W	1.13×10^{-3}	2.53×10^4	183.85
Zn	1.03×10^{-3}	8.22×10^3	65.38
Zr	2.56×10^{-2}	2.95×10^5	91.22
CN ⁻	4.01×10^{-4}	1.27×10^3	26.0177
NH ₃	1.21×10^{-2} 5.43×10^{-3}	2.51×10^4 1.13×10^4	17.0304
CO ₃ ⁻²	1.11×10^{-1}	8.13×10^5	60.0092
Cl ⁻	8.48×10^{-2} 7.37×10^{-2}	3.67×10^6 3.19×10^5	35.453
F ⁻	7.14×10^{-1} 5.02×10^{-1}	1.55×10^6 1.16×10^6	18.9984
SO ₄ ⁻²	7.16×10^{-2}	8.39×10^5	96.0576
NO ₃ ⁻	2.74 2.75	2.07×10^7 2.08×10^7	62.0049
NO ₂ ⁻	5.04×10^{-1}	2.33×10^6	46.0055
PO ₄ ⁻³	3.07×10^{-2}	3.56×10^5	94.9714
OH ⁻	1.15	2.39×10^6	17.0073

Waste Component: Radionuclides	Total Feed: Concentration (μ Ci/L) ^(a)	Total Inventory (Ci) ^(a)	Half-Life (years) ^(a)
³ H	5.07 5.12	6.19×10^2 6.25×10^2	12.3
¹⁴ C	2.00	2.44×10^2	5730
⁶⁰ Co	2.73×10^1	3.33×10^3	5.27
⁶³ Ni	1.19×10^2	1.45×10^4	100
⁷⁵ Se	3.0	3.56×10^2	6.5×10^4
⁹⁰ Sr	1.29×10^4	1.57×10^6	29.1* (28.5)
⁹⁵ Zr	1.73×10^3	2.11×10^5	0.1752 (64 day)

Table 2.4. (contd)

Waste Component: Radionuclides	Total Feed: Concentration ($\mu\text{Ci/L}$) ^(a)	Total Inventory (Ci) ^(a)	Half-Life (years) ^(a)
⁹⁴ Nb	1.30×10^3	1.59×10^1	2.00×10^4
⁹⁵ Nb	1.78×10^3	2.17×10^5	0.1752 ^(b) (64 day)
⁹⁹ Tc	5.17×10^1	6.31×10^3	2.13×10^5
¹⁰³ Ru	1.29×10^2	1.57×10^4	0.1076 (39 day)
¹⁰⁶ RuRh ^(b)	1.84×10^3	2.24×10^5	1.020
¹¹³ Sn	1.78×10^2	2.17×10^4	0.31485 (115 day)
¹²³ Sb	5.41×10^2	6.60×10^4	2.73
¹²⁶ Sn	9.1	1.11×10^3	1.0×10^5
¹²⁹ I	1.2×10^1	1.46×10^1	1.57×10^7
¹³⁴ Cs	3.19×10^2 3.18×10^2	3.89×10^4 3.88×10^4	2.07
¹³⁵ Cs	0.69	8.42×10^1	2.3×10^6 (3.0×10^6)
¹³⁷ Cs	1.32×10^5	1.61×10^7	30.2
¹⁴⁴ CePr ^(b)	1.55×10^3	1.39×10^5	0.7803 (285 day)
¹⁵² Eu	4.08	4.98×10^2	13.5 ^(a)
¹⁵⁴ Eu	1.49×10^2 9.73×10^1	1.32×10^4 1.19×10^4	8.59 ^(a) (8.3)
¹⁵⁵ Eu	1.67×10^2	2.04×10^4	4.71 ^(a) (4.96)
²⁰⁴ Rn	3.0×10^{-4} 4×10^{-6}	3.66×10^{-1} 4.83×10^{-4}	1600
²⁰⁷ Pb	2.1×10^{-1} 3.1×10^{-3}	2.93×10^{-1} 3.78×10^{-1}	7.54×10^4
²³⁴ U	3.37×10^{-1} 4.45×10^{-2}	4.11×10^1 5.43	2.454×10^5
²³⁵ U	1.97×10^{-1} 2.71×10^{-3}	2.40 3.31×10^{-1}	7.037×10^8
²³⁸ U	7.24×10^{-1} 1.04×10^{-2}	9.69 1.27	4.468×10^9
²³⁹ Np	4.39×10^{-1}	5.36×10^1	2.140×10^6
²⁴⁰ Pu	1.59×10^{-1}	1.94×10^1	87.7

WHC-SD-WM-EE-004, Rev. 0

Table 2.4. (contd)

Waste Component: Radionuclides	Total Feed: Concentration ($\mu\text{Ci/L}$) ^(a)	Total Inventory (Ci) ^(a)	Half-Life (years) ^(a)
^{239,240} Pu ^(b)	2.59	3.16×10^2	2.41×10^4
²⁴¹ Pu	8.90	1.09×10^3	14.4
²⁴² Pu	1.57×10^{-5}	1.92×10^{-3}	3.75×10^5 * (3.763×10^5)
²⁴¹ Am	2.33×10^1	2.84×10^3	433
²⁴³ Cm	4.14×10^{-2}	5.05	29.1* (28.5)
²⁴⁴ Cm	5.28×10^{-2}	6.44	18.1

- (a) Total feed values are as they appear in Appendix E (from Hendrickson and Conner 1993).
- (b) Total inventory in kilograms of chemical was generated by multiplying total feed concentration by waste volume (1.220×10^5 L) and by molecular weight, and then converting from grams to kilograms.
- (c) Total feed values are as they appear in Appendix E (from Hendrickson and Conner 1993). Inventory estimates of some radionuclides changed by less than 2% between the start and end of modeling due to correction of rounding errors in the inventory estimation. The inventory of europium-152 changed significantly but is negligible in all cases due to its short half-life. In all cases, the final inventory used in the central compliance case is shown.
- (d) Total inventory in curies of radionuclide was generated by multiplying total feed concentration by waste volume (1.220×10^5 L) and converting μCi to Ci units.
- (e) Half life values used in the transport simulations are from Browne, Firestone, and Shirley (1986). Half-lives marked with an asterisk are from Walker, Parrington, and Feiner (1989). The Walker et al. half-lives superseded the Browne et al. values for simulation of the central compliance case. Other compliance cases and sensitivity cases used the Browne et al. half-life value provided in parenthesis. The Walker et al. values are used in Appendix E. A correction to the europium-152 half-life from 1.5 years to 13.5 years was made after initial simulations had been performed.

ADDITIONAL INFORMATION FOR DOSE ASSESSMENT

Dose estimates for the Grout Disposal Facility Performance Assessment (PA) as a result of groundwater transport were largely due to the radionuclides Tc-99 and I-129 that would be contained in the waste stream. The dose to a maximally exposed individual from radionuclides in the grout facility was evaluated for intake of 2 L/day of contaminated drinking water, and also for "all pathways" scenarios where an individual was assumed to obtain a fraction of his diet from a family farm or garden irrigated with contaminated groundwater. In modeling the transport and consequences following disposal of these radionuclides, they were assumed to be mobile in the subsurface environment and therefore were transported relatively rapidly to groundwater as compared to less mobile constituents. The calculated dose for both radionuclides in the "family farm" scenario was essentially all due to ingestion of drinking water and milk produced on irrigated pasture. The specific parameters used to determine the doses for these radionuclides are thus of particular interest, and are described in the following sections and a summary table. Most are also listed in Appendix I of the PA.

SOIL/WATER PARTITION COEFFICIENT

The distribution or adsorption coefficients (K_d) for Tc-99 and I-129 are not used directly in the GENII food chain models, but they are reflected in the leaching factor used to describe removal of radionuclides from surface soil by irrigation. The value of the leaching factor depends on the adsorption coefficient in addition to a number of other parameters, and represents the fraction of deposited radionuclide that is removed from the surface soil layer each year. In this assessment, the leaching factor for both Tc and I is 0.8/yr, which implies a $K_d = 0$, consistent with the assumption used for modeling groundwater transport.

Use of this high leaching factor for Tc and I results in their relatively rapid removal from surface soil, thereby reducing root uptake. However, root uptake is somewhat less important as a transport pathway into the food chain than direct deposition via irrigation on edible plants and pasture grass. The leaching factor was not evaluated as part of the sensitivity analysis.

CONCENTRATION FACTORS AND BIOACCUMULATION FACTORS

The attached table lists the element-specific values used in this analysis for soil-to-plant concentration ratios, transfer factors for incorporation into animal products, and bioaccumulation factors for freshwater fish. The values for these factors are generally taken from recent reviews of published literature, and the references indicated in the table represent the most direct source of the values, followed by any other primary or secondary references cited by the first source. In most cases, the values reported in the literature were screened as part of the GENII code development some years ago, or during preparation of the NRC document, NUREG/CR-5512, to determine the general quality of the data and their applicability to the environmental setting at Hanford. Where there was no other basis on which to discriminate between possible estimates for a given parameter, the more conservative value was generally chosen (i.e. the value that would ultimately yield the highest dose result in the food chain model). The best documentation for the parameter selection and the sources for the parameters currently used in the PA are the most recent revision of PNL-3777 (Rev. 2, see reference A below), and NUREG/CR-5512 (see reference C). The bioaccumulation and concentration factors were not included in the sensitivity analysis done for the PA.

DOSE CONVERSION FACTORS

Dose conversion factors and the associated GI uptake (f₁) factors used in the PA assessment are also listed in the attached table. In general, these parameters follow the recommendations of the ICRP in its publications 26, 30, and 48, which are also reflected in the recommended values adopted by the U.S. Department of Energy (references H and I).

The actual values used in the PA assessment for internal dose conversion factors may differ somewhat from the DOE recommended values because the GENII code calculates these values (using the ICRP model) for a specific dose commitment period rather than reading the values from a data library. The largest variance is for ingestion of Tc-99, which is about 70% higher than the published DOE value; the other internal dose conversion factors are within 10-20% of the DOE recommendations (specific differences are noted in the attached table). The differences in dose conversion factors are generally due to minor variations from the ICRP metabolic models for technetium and iodine that were incorporated into the GENII code as a result of external reviews during the code development process. The differences reflect information that has become available since the basic ICRP models were developed in the late 1970s, or features that were added to the GENII models to permit estimation of dose to nonstandard individuals, (e.g., fetus exposure to I-129 from mother's intake).

The f₁ values incorporated into the dosimetry model are also consistent with DOE recommendations, which are identical for all chemical forms of technetium and iodine (reference H). The lung retention class assumed for the inhalation dose conversion factors was chosen to yield the maximum dose for this pathway, although inhalation contributed a negligible fraction of the total dose for the "all pathways" scenarios.

The peak dose reported in the PA for the "all pathways" scenarios (i.e. the family farm or garden scenarios) is essentially all due to ingestion of Tc-99 and I-129, with roughly comparable contributions from each radionuclide. Therefore the doses reported in the PA may differ somewhat from those that would be calculated using the DOE recommended dose factors directly, as a result of minor differences in the metabolic models. The implication for the PA analysis is that the reported doses from Tc-99 in the "all pathways" scenarios are higher by about 70%, and the total doses by 30-40%, relative to those that would be calculated using the DOE recommended values. The drinking water pathway doses are not affected, because they were calculated in a spreadsheet using the DOE recommended dose factors rather than with the GENII code.

The external dose conversion factors are also consistent with DOE recommendations (reference I), except in the case of exposure to the contaminated ground surface. The DOE recommended dose factors are based on an infinite plane geometry, which is appropriate for exposure scenarios where the radionuclides are deposited on the soil surface. This assumption is realistic for accidental release scenarios where the ground surface is not disturbed, however it is conservative for chronic exposure situations where the surface is cultivated or irrigated and radionuclides are mixed into a significant volume of soil. In the PA assessment, the radionuclides were assumed to be uniformly mixed in the upper 15 cm of soil, which results in a substantially lower dose for low-energy gamma emitters such as Tc-99 and I-129 because of shielding by the upper soil layer. This approach is more appropriate for a scenario where the receptor is exposed to contaminated ground following plowing or irrigation, which would transport mobile radionuclides such as Tc-99 or I-129 below the soil surface. Because external dose was an insignificant fraction of the total dose for these radionuclides in the "all pathways" scenarios, the difference in external dose factors did not affect the doses reported for the PA analysis.

Parameters used to Estimate Dose from Technetium-99 and Iodine-129 in the Grout Disposal Facility Performance Assessment

Parameter Description	Tc-99		I-129	
	Value	Reference	Value	Reference
Leaching Factor/ Kd Assumed for LF	0.8 0.0	A, B	0.8 0.0	A, B
Soil/Plant Transfer (Ci/g dry wt edible plant per Ci/g dry wt soil)		C, D, E		C, D, E
Leafy Vegetables	4.4E+01		3.4E-03	
Other Vegetables	1.1E+00		5.0E-02	
Fruit	1.5E+00		5.0E-02	
Grain	7.3E-01		5.0E-02	
Animal Product Transfer (concentration in edible product per daily intake rate)		C, B, E, F		C, B, E, F
Beef & Pork (Ci/kg per Ci/day)	8.5E-03		7.0E-03	
Poultry (Ci/kg per Ci/day)	3.0E-02		1.8E-02	
Milk (Ci/L per Ci/day)	1.0E-02		1.0E-02	
Eggs (Ci/kg per Ci/day)	3.0E+00		2.8E+00	
Aquatic Bioaccumulation (ratio of concentration in edible flesh to concentration in fresh water)		A, G		A, G
Fish (Ci/kg per Ci/L)	1.5E+01		5.0E+01	
GI Uptake F1/ Lung Retention Class	8.0E-01 W	H	1.0E+00 D	H
Dose Conversion Factors (all pathways scenarios)		B, I		B, I
Inhalation (rem/ μ Ci intake)	8.6E-03 (+15%)*		1.5E-01 (-17%)*	
Ingestion (rem/ μ Ci intake)	2.2E-03 (+70%)*		2.5E-01 (-11%)*	
Soil Surface (mrem/yr per μ Ci/m ³)	3.7E-04		4.1E-02	
Water Immersion (mrem/yr per μ Ci/m ³)	6.2E-06		1.1E-01	

* These values indicate the relative difference between the dose conversion factors as calculated by the GENII code and the DOE recommended values (reference H).

References:

- A. Schreckhise, R. G., K. Rhoads, J. S. Davis, B. A. Napier, and J. V. Ramsdell. 1993. Recommended Environmental Dose Calculation Methods and Hanford-Specific Parameters. PNL-3777, Rev. 2. Pacific Northwest Laboratory, Richland Washington.
- B. Napier, B. A., D. L. Streng, R. A. Peloquin, and J. V. Ramsdell. 1988. GENII -The Hanford Environmental Radiation Dosimetry Software System. PNL-6584, Vol. 1 - Conceptual Representation, Vol. 2 - Users' Manual, Vol. 3 - Code Maintenance Manual. Pacific Northwest Laboratory, Richland, Washington.
- C. Kennedy, W. E., Jr. and D. L. Streng. 1992. Residual Radioactive Contamination from Decommissioning. NUREG/CR-5512, PNL-7994, Vol. 1, Prepared for the U. S. Nuclear Regulatory Commission by Pacific Northwest Laboratory, Richland, Washington.
- D. International Union of Radioecologists. 1989. Sixth Report of the Working Group on Soil-to-Plant Transfer Factors. RIVM, Bilthoven, The Netherlands.
- E. Baes, III, C. F., R. D. Sharp, A. L. Sjoeren, and R. W. Shor. 1984.. A Review and Analysis of Parameters for Assessing Transport of Environmentally Released Radionuclides Through Agriculture. ORNL-5786, Oak Ridge National Laboratory, Oak Ridge Tennessee.
- F. Ng, Y. C., C. S. Colsher, and S. E. Thompson. 1982. Transfer Coefficients for Assessing the Dose from Radionuclides in Meat and Eggs. NUREG/CR-2976, U.S. Nuclear Regulatory Commission, Washington, D.C.
- G. Poston, T. M. and D. C. Klopfer. 1986. A Literature Review of the concentration Ratios of Selected Radionuclides in Freshwater and Marine Fish. PNL-5484, Pacific Northwest Laboratory, Richland Washington.
- H. U.S. Department of Energy (DOE). 1988. Internal Dose Conversion Factors for Calculation of Dose to the Public. DOE/EH-0071, DOE Assistant Secretary for Environment, Safety, and Health, Washington, D.C.
- I. U.S. Department of Energy (DOE). 1988. External Dose-Rate Conversion Factors for Calculation of Dose to the Public. DOE/EH-0070, DOE Assistant Secretary for Environment, Safety, and Health, Washington, D.C.

ATTACHMENT No. 5

Rev 1 of the waste feed projection document:

Hendrickson, D.W., and J.M. Conner. February 1994. Grout Treatment Facility Waste Feed Projections. WHC-SD-WM-TI-528, Rev.1.
Westinghouse Hanford Company, Richland, Washington.

WHC-SD-WM-TI-528, Rev. 1

**GROUT TREATMENT FACILITY
WASTE FEED PROJECTIONS**

Prepared for
WESTINGHOUSE HANFORD COMPANY

by

D. W. Hendrickson
Westinghouse Hanford Company

J. M. Conner
Westinghouse Hanford Company

February 1994

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1

Grout Treatment Facility Waste Feed Projections

TABLE OF CONTENTS

	<u>Page</u>
1.0 INTRODUCTION	1-1
2.0 WASTE DATA EVALUATION METHODS AND HISTORY	2-1
2.1 Wastes Described by Direct Sampling and Analysis	2-1
2.2 Wastes Described by Process and Transfer History	2-2
2.3 Wastes Described by Pretreatment Flowsheets	2-4
3.0 DATA HANDLING TECHNIQUES	3-1
3.1 Data Handling for Existent Waste Samples	3-3
3.1.1 Existent Dilute Waste Sample Data	3-4
3.1.2 Existent Concentrated Waste Sample Data	3-4
3.2 Data Handling for Process History Samples	3-5
3.2.1 Referenced Historical Process Analyses	3-5
3.2.2 Future Evaporator Product Estimation	3-5
3.2.3 Process Analyses for Previous Evaporator Products	3-6
3.3 Data Handling for Pretreatment Low-Level Streams	3-9
3.4 Data Summarization and Interpretation	3-10
3.4.1 Application of Uniform Decay Date	3-10
3.4.2 Evaluation of Dilute Waste Requirements	3-11
3.4.3 Use and Application of Limiting Values	3-12
3.4.4 Analytical Errors	3-13
3.4.5 Data Summary	3-14
3.5 Recommendations on Data Usage	3-15
4.0 SPECIAL ESTIMATES OF CRITICAL ISOTOPES	4-1
4.1 ¹³⁵ Cesium Estimation	4-1
4.1.1 Back-Decay of ¹³⁷ Cesium Data	4-2
4.1.2 ¹³⁵ Cesium Production	4-3
4.1.3 ¹³⁵ Cesium Estimate Usage	4-4
4.2 ²³⁷ Neptunium Estimation	4-4
4.2.1 Revision of ²⁴¹ Americium Estimates	4-5
4.2.2 Revision of ²³⁷ Neptunium Estimates	4-8
4.3 ²²⁶ Radium Estimation	4-9
4.4 ¹²⁹ Iodine Estimation	4-11
4.5 ¹²⁶ Tin Estimation	4-12
4.6 ⁹⁹ Technetium Estimation	4-12
4.7 ⁹⁴ Niobium Estimation	4-13
4.8 ⁷⁹ Selenium Estimation	4-13
4.9 ¹⁴ Carbon Estimation	4-13
4.10 ²³⁸ Uranium Estimation	4-14
4.11 Special Estimate Summary	4-15
5.0 REFERENCES	5-1
APPENDIX	A-i

WHC-SD-WM-TI-528, Rev. 1

LIST OF TABLES

<u>TABLE</u>	<u>Page</u>
1: Grout Treatment Facility Waste Volume Expectations	2-2
2: Tank 241-AN-104 Waste Source History	3-7
3: Tank 241-AN-105 Waste Source History	3-8
4: Grout Treatment Facility Waste Projection	3-18
5: ORIGEN2 Yield Per Metric Ton of Fuel	4-2
6: Waste ¹³⁷ Cs Activity	4-4
7: ²⁴¹ Americium Sources	4-6
8: Special Estimates of Critical Isotopes	4-16

LIST OF FIGURES

	<u>Page</u>
Figure 1: Waste Source Volume Distribution for Grout Disposal .	2-3
Figure 2: Grout Feed Material Data Flowsheet	3-2
Figure 3: Profile of DSSF Family Wastes Relative to Sodium . .	3-3
Figure 4: Distribution of Am-241 Sources to Grout (Assumes maximum allowable in 4AN/5AN)	4-7

WHC-SD-WM-TI-528, Rev. 1

GROUT TREATMENT FACILITY
WASTE FEED PROJECTIONS

1.0 INTRODUCTION

The *Final Environmental Impact Statement, Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington* [HDW-EIS] (DOE 1987) evaluated disposal alternatives for Double-Shell Tank (DST) wastes at the Hanford Site. The responsive Record of Decision [ROD] (DOE 1988) selected cementitious disposal via the Hanford Grout Disposal Program (HGDP) as the preferable alternative for the disposal of low-level radioactive liquid wastes contained in Hanford's DSTs.

Since the issuance of the HDW-EIS and ROD (DOE 1987, 1988) extensive review and analysis has been conducted to determine the specific nature and characteristics of DST wastes to be received and disposed under the HGDP.

The purpose of this document is to describe the current information available on the character of wastes identified as HGDP feed material. Grout feed material is to be composed of the low-level liquid pretreated residuals and supernatant fractions of all DSTs. Dilute waste materials contained within DSTs are, in large part, expected to be evaporated prior to HGDP processing in order to ease tank farm capacity constraints.

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1**2.0 WASTE DATA EVALUATION METHODS AND HISTORY**

The DST wastes described in this document have been evaluated in four general manners. The first such manner is that of direct sampling and analysis for the purpose of characterization. The second is the use of historical process data surrounding material transfers and historical and expected Evaporator/Crystallizer campaign conduct. Thirdly, pretreatment flowsheet information is used to describe approximately one half of expected waste receipts to the HGPD. Finally, data resulting from the above evaluations are compared to relevant reactor history codes and Hanford Site documents. This last comparative evaluation is contained in §4.0.

A summary of expected wastes described in this document is contained in Table 1 and depicted in Figure 1. These wastes comprise the supernatant liquid fraction of current, future and pretreated DST contents expected to be received by the Hanford Grout Disposal Program. These wastes and their volumes are described by Hanlon (1992), and Lowe (1991), and are further developed within this document.

2.1 Wastes Described by Direct Sampling and Analysis

The DST wastes described in this document for which information gathered was by direct sampling and analysis include concentrated waste tanks 241-AN-106, 241-AW-101, and 241-AN-103, and dilute waste tanks 241-AP-103, 241-AW-106, and 241-AW-102. Further discussion of the history of information accumulation on this waste category is provided below.

The first significant milestone in the evaluation of concentrated DST wastes was achieved in 1988 with the initial issuance of "Methods and Data for Use in Determining Source Terms for the Grout Disposal Program" (Hendrickson 1990). That document describes the analyses of the supernatant fractions of three DST waste tanks expected, at that time, to be representative of all wastes to be received at the HGPD. The three wastes discussed were those contained in tanks 241-AN-106, 241-AW-101, and 241-AN-103. These wastes are, respectively, concentrated phosphate wastes from N-Reactor, concentrated Facilities waste termed Double-Shell Slurry Feed (DSSF), and Double-Shell Slurry (DSS).

Additional milestones were achieved in the completion of detailed analyses of tanks 241-AN-106 and 241-AW-101 (Welsh 1991a and 1991b). These detailed analyses allowed significant analytical refinement and reduction in the estimation of waste variability (expressed as the standard deviation) for these wastes.

Characterization efforts in support of projected Evaporator/Crystallizer operation led to the sampling and analysis of dilute non-complexed wastes contained in tanks 241-AP-103, 241-AW-106, and 241-AW-102 between June and December 1991.

WHC-SD-WM-TI-528, Rev. 1

TABLE 1: Grout Treatment Facility Waste Volume Expectations			
General Type	Description	Tanks	Volume (L x 10 ⁶)
DSSF ¹ Family	Concentrated Phosphate	241-AN-106	3.67
	Existent DSSF	241-AW-101	3.83
		241-AP-105	3.15
		241-AN-104	3.02
		241-AN-105	4.27
	Future DSSF	Undefined	30.28
	DSS	241-AN-103	3.55
	Dilute Wastes	241-AP-106 and others	9.05
Pretreated Wastes (Low-Level Residual)	NCAW	241-AZ-101	3.60
		241-AZ-102	3.61
	NCRW	241-AW-103	12.87
		241-AW-105	
	PFP	241-SY-102 and PFP	2.08
	Complexed Concentrate	241-SY-101 241-SY-103 241-AN-102 241-AN-107	39.0
Total			122.0

2.2 Wastes Described by Process and Transfer History

Wastes described in this document for which information gathered was by process and transfer history include concentrated waste tanks 241-AP-105, 241-AN-104, and 241-AN-105, and dilute waste tank 241-AP-106. Future evaporator products are estimated based on current dilute waste compositions and expected evaporative processing. Further discussion of the history of information accumulation on this waste category is provided below.

Detailed historical analysis of waste material transfers and Evaporator/ Crystallizer operation allowed the development of waste composition estimates for dilute waste tank 241-AP-106 and DSSF tank 241-AP-105 (Hendrickson and Welsh 1992a, and 1992b). These material estimates were developed to support sampling and analysis of these tanks.

Waste descriptions and acronyms are detailed in the following text and in Hanlon (1992).

WHC-SD-WM-TI-528, Rev. 1

Figure 1: Waste Source Volume Distribution for Grout Disposal

Dilute wastes contained in tanks 241-AP-103, 241-AW-106, and 241-AW-102, as described in §2.1, were sampled and analyzed in support of Evaporator/ Crystallizer operation. These materials are intended to be evaporated in 242-A Evaporator/Crystallizer Campaign 93-1 (O'Rourke 1992). As these materials are miscellaneous facilities wastes, and as the source streams are expected to be the generation source for such future wastes, process evaluation of the evaporated [i.e. concentrated] product has been conducted to estimate the composition and concentration of future concentrated wastes. As described by O'Rourke, expectations are that the concentrated materials would not be as highly concentrated as current DSSSF material and would be classified as dilute-DSSSF wastes (DDSSF). Such concentrated product is, as depicted in Figure 1, expected to constitute approximately 25 percent of all HGD feed material.

Concentrated waste materials (DSSF) contained within tanks 241-AN-104 and 241-AN-105 were produced in Evaporator/Crystallizer campaigns 84-3, 84-5, and 85-3. These campaigns, and sample data in support of evaporator operation, are documented in Certa (1985), Gratny (1985), and Pontious (1986). Waste volumes, and their analyses, distributed to these tanks were used to estimate the composition of these wastes.

WHC-SD-WM-TI-528, Rev. 1

2.3 Wastes Described by Pretreatment Flowsheets

Wastes described in this document for which information gathered was from pretreatment flowsheets include the low-level streams resulting from pretreatment of Neutralized Current Acid Waste (NCAW), Neutralized Cladding Removal Waste (NCRW), Plutonium Finishing Plant (PFP) waste, and Complexed Concentrate (CC) waste.

NCAW is currently stored in tanks 241-AZ-101 and 241-AZ-102. NCRW is currently stored in tanks 241-AW-103 and 241-AW-105. PFP waste is currently stored in 241-SY-102 and in the PFP. CC waste is currently stored in DST and SST tanks 241-SY-101 and -103, 241-AX-102 and -103, and 241-AN-102 and -107 (Hanlon 1992).

These wastes and the low-level streams resulting from their pretreatment are described in Lowe (1991). These flowsheets include globally the existence and pretreatment of CC waste within the single-shell tanks (SST) 241-AX-102 and 241-AX-103. Although this document is prepared to describe the disposal of DST wastes only, the differences in waste volume and contents due to the small volume of these SST contents (151 kgal) upon the Lowe (1991) flowsheets are conservatively neglected in this document.

WHC-SD-WM-TI-528, Rev. 1

3.0 DATA HANDLING TECHNIQUES

As described in §2.0, above, three general forms of data were available for compilation and interpretation. In reiteration, these forms of data were actual sample data of existent tank wastes, sample and process data for wastes placed (or to be placed) into tanks, and process flowsheet estimates for future pretreatment residuals. The handling of each of these types of data are described below. Each of the data handling operations described below is depicted in Figure 2.

Key to the handling of data within the first two categories (data based upon direct sampling or evaporative processing of current and future wastes which will not be pretreated) is the knowledge that the sources for these wastes are common. Each of these wastes are the combined product of the miscellaneous low-level liquid wastes of Hanford's 100, 200, 300, and 400 Areas. Because the waste sources are similar they constitute a family which is herein described as the "DSSF Family" of wastes. Within this "family" the concentration of nonvolatile constituents is inversely proportional to water content. This familial relationship, as illustrated in Figure 3, is not perfect but allows data gaps to be bridged and the mean concentration of an analyte to be reasonably estimated in the absence of some data. As an example, if potassium concentrations are described for four of six tanks in the family, the mean of all six tanks is represented as the mean of the four tanks for which data is provided.

As will be described in §3.3, the conduct of pretreatment operations and the data provided do not allow handling of data in the manner of the DSSF family. This data is recognized to be incomplete, as not all analytes were followed through the flowsheets and because the differing nature of the sources do not allow one to make generalizations based on similarity of waste sources. In addition, proposed treatment regimes differ for the various waste streams. Thus, in totalizing expected waste streams from these operations, the mean of all waste streams was calculated as the weighted average of all streams. If no data was provided for an analyte in a stream, the weight assigned was zero while the volume of that stream remained a part of the calculation. This may introduce some non-conservative estimates for some analytes; however, it is believed that most analytes of potential concern in large streams are reported and form the basis of this family's estimate.

Summary tables for the work described in §§3.1 through 3.4 are contained in Tables 1-1 through 1-4 of the Appendix. All data are converted to units of $\mu\text{Ci/L}$ for radionuclides, and molarity for other constituents unless specifically noted. All radionuclide data are decayed to October 1, 1993, unless specifically noted; further discussion of decay is provided in §3.4.

Figure 2: Grout Feed Material Data Flowsheet

WHC-SD-WM-TI-528, Rev. 1

Figure 3: Profile of DSSF Family Wastes Relative to Sodium

3.1 Data Handling for Existent Waste Samples

Two types of existent waste have been directly sampled for the purpose of characterization. These wastes are dilute non-complexed wastes and concentrated wastes. In all, these data describe the contents of six DSTs. Data flows shown in Figure 2 for such direct sampling are initiated with the symbol of a circle (○).

WHC-SD-WM-TI-528, Rev. 1

3.1.1 Existent Dilute Waste Sample Data

Data described in this category includes sample data taken for dilute waste tanks 241-AP-103, 241-AW-106, and 241-AW-102. The sample constituent mean for these tanks was calculated as:

$$Mean_i = \frac{\sum_{j=1}^n [C]_j \times Volume_j}{\sum_{j=1}^n Volume_j} \quad [Eq. 3.1]$$

Where: [C] = constituent concentration,
 i = constituent identifier,
 j = sample, tank, or stream identifier,
 Volume_j is assigned a value of zero when [C]_j is unreported.

Tables 2-1, 2-2, and 2-3 of the Appendix contain the validated data for these dilute waste samples supporting O'Rourke (1992).

Tables 2-4, 2-5, and 2-6 of the Appendix contain the calculated summaries, by tank, of this analytical data. Appendix Table 1-1 contains a joint summary of these dilute wastes and includes an estimate of 241-AP-106 (Hendrickson and Welsh 1992a). These four tanks of dilute waste are used herein to describe future dilute waste receipts. Evaluation of expected evaporator operation for tanks 241-AP-103, 241-AW-106, and 241-AW-102 is calculated and displayed in Appendix Table 2-7 and included within Appendix Table 1-2; further discussion on this matter is provided in §3.2.2.

3.1.2 Existent Concentrated Waste Sample Data

Data described in this category includes sample mean data of concentrated waste tanks 241-AN-106 (Welsh 1991a), 241-AW-101 (Welsh 1991b), and 241-AN-103 (Hendrickson 1990). These data are incorporated in Appendix Tables 4-1 and 4-2. These tables do not embody any manipulation of the data other than unit conversion.

Particular aspects of the determination and use of the means for these tanks are embodied within the respective reference document, however, the following short summary is deemed appropriate.

Tank 241-AN-106 (Welsh 1991a) was sampled with the process knowledge that the tank was stratified into a high-phosphate concentration layer, a high-sulfate concentration layer, and at least one intermediate composition boundary layer. Twelve bottle-on-string samples of the waste were extracted and analyzed. Statistical analysis of the data indicated that the tank was indeed stratified and that the tank would be well represented by a stratified mean and sample deviation.

WHC-SD-WM-TI-528, Rev. 1

Tank 241-AW-101 (Welsh 1991b) was sampled with the expectation that the tank was relatively homogeneous. Twelve bottle-on-string samples were extracted and analyzed. Statistical analysis of the data indicated that the tank was homogeneous.

Tank 241-AN-103 (Hendrickson 1990) was sampled through core-drilling of the tank. The samples analyzed and reported were those of core composites.

3.2 Data Handling for Process History Samples

Both dilute and concentrated wastes are herein described by their evaporative process and analytical history. This category includes the dilute waste tank 241-AP-106, DSSF tanks 241-AP-105, 241-AN-104, and 241-AN-105, and future concentrated miscellaneous wastes. Data flows shown in Figure 2 for such evaporative process history and analysis are initiated with the symbol of a triangle (Δ).

3.2.1 Referenced Historical Process Analyses

As described in §2.2, the contents, in terms of expected mean concentrations, of tanks 241-AP-106 and 241-AP-105 were estimated in Hendrickson and Welsh (1992a and 1992b). Appendix Table 1-1, containing a joint estimate of dilute wastes, incorporates 241-AP-106 estimates. Appendix Table 4-2 contains waste tank 241-AP-105 estimates. Each are, again, converted to the common units of $\mu\text{Ci/L}$ and molarity except where noted.

3.2.2 Future Evaporator Product Estimation

The composition of concentrated miscellaneous wastes, as introduced in §§2.2 and 3.1.2, has been estimated to be represented by the evaporative product of tanks 241-AP-103, 241-AW-106, and 241-AW-102. Table 2-7 of the Appendix details the expected composite of these tanks and their boil-down. Non-volatile constituent concentrations are calculated as:

$$\text{Concentrated Mean}_i = \frac{\text{Non-Concentrated Mean}_i}{(1 - \text{WVR})} \quad [\text{Eq. 3.2}]$$

Where: WVR = $(1 - S/F)$ = Waste Volume Reduction factor (0.87),
 S = Slurry Volume (concentrated product),
 F = Feed Volume, and
 Non-Concentrated Mean_i is evaluated by Equation 3-1.

The 87% WVR used herein is that described by O'Rourke (1992) for expected Evaporator/Crystallizer operations. Thirty million liters (8×10^6 gallons) of this product, derived from Koreski and Strode (1992), are used in this estimate.

WHC-SD-WM-TI-528, Rev. 1

Volatile constituent concentrations (ammonia/ammonium and tritium) are calculated to be removed in the same ratio as water as:

$$\text{Concentrated Mean}_i = \text{Non-Concentrated Mean}_i \times \frac{\left(1 - \left(\frac{y_1}{z_1}\right) WVR\right)}{(1 - WVR)} \quad [\text{Eq. 3.3}]$$

Where: y_1 = molar density of pure water condensate (mol/L),
and
 z_1 = molar density of water in feed (mol/L).

3.2.3 Process Analyses for Previous Evaporator Products

The current volumes of DSSF material contained within tanks 241-AN-104 and 241-AN-105 were generated in Evaporator campaigns 84-3, 84-5, and 85-3 (Certa 1985; Gratny 1985; and Pontious 1986).

A brief synopsis of transfer history, derived from operating records, relating to the generation sources of these materials is contained in Tables 2 and 3. Each of these tanks contained a small heel of dilute non-complexed waste or concentrated waste prior to the introduction of current materials.

WHC-SD-WM-TI-528, Rev. 1

TABLE 2: Tank 241-AN-104 Waste Source History			
Date	Activity	Volume (Kgal) Transferred	Tank Volume (Kgal) at Completion
Heel Present from Prior Activities			61
3/4/84	Evaporator Campaign 84-3 product to tank	290	351
4/84	Measured water loss	-3	348
9/84	Transfer to 3AN	-193	155
10/5/84	Evaporator Campaign 84-5 product to tank	782	937
2/85	Measured water gain	3	940
4/6/85	Evaporator Campaign 85-3 product to tank	121	1,061

* Note: Shaded cells are those pertinent to calculations and analytical data.

WHC-SD-WM-TI-528, Rev. 1

TABLE 3: Tank 241-AN-105 Waste Source History			
Date	Activity	Volume (Kgal) Transferred	Tank Volume (Kgal) at Completion
Heel Present from Prior Activities			11
12/82	Evaporator Campaign 83-2 product to tank	259	270
1/83	Evaporator Campaign 83-4 product to tank	369	639
3/84	Transfer	-30	609
3/84	Transfer from 4AN	499	1,108
2/85	Transfer to Evaporator	-954	154
3/85	Evaporator Campaign 85-3 product to tank	239	393
4/85	Evaporator Campaign 85-3 product to tank	732	1,125

* Note: Shaded cells are those pertinent to calculations and analytical data.

For purposes of this estimation, the existent volumes were assumed to be the represented by the materials introduced. This is considered a reasonable approximation. Upon inspection of Table 2 one should observe that only 5% of the current contents of 241-AN-104 consist of materials present prior to the data applied. Similarly, approximately 14% of material present in 241-AN-105 was previously present; this material was dilute-DSSF.

Evaporator campaign 84-3, 84-5, and 85-3 data are presented in Appendix Tables 3-1, 3-2, and 3-3. Calculations upon this data are summarized on Appendix Tables 3-4 and 3-5, which include the decay of radioisotopes to the date of October 1, 1993. The method and selection basis for this decay date are described in §3.4, below.

WHC-SD-WM-TI-528, Rev. 1

The contents of tanks 241-AN-104 and 241-AN-105 are described in relation to analytical data supporting the above evaporator campaigns and the volumes received. Material transfers and minor discrepancies between transfer records and campaign post-run documentation result in the application of the following volumes (kgal) of materials in the estimation of material concentrations:

<u>Evaporator Campaign</u>	<u>241-AN-104 Contribution</u>	<u>241-AN-105 Contribution</u>
84-3	148.5	0
84-5	790	0
85-3	121	971

Thus, the analyses supporting the above volumes generated are weighted by volume to calculate the mean contents of these tanks in the manner of Equation 3-1. The resulting estimations for these tanks are contained in Appendix Table 4-3, decayed to the latest date of the above samples (April 1985).

3.3 Data Handling for Pretreatment Low-Level Streams

At this time it is believed that Lowe (1991), provides the most complete and current estimate of material balances for pretreatment streams. Lowe's flowsheets are a function of what is currently known about NCAW, NCRW, CC, and PFP wastes and how they are currently planned to be pretreated. The pretreatment regimens are intended to separate a low volume of high level and transuranic material for deep geologic disposal from a large volume of low-level waste for near-surface disposal. The separation technology development and implementation is, admittedly, far from complete and subject to political, public perception, and funding variances. With this in mind, Lowe's flowsheets have been assigned an impact and quality assurance level consonant to no external review. As such, data used in this document are directly (some unit conversions) from this reference as no comparable data source exists. Should it become necessary to guide and require further pretreatment, the acceptance criteria for wastes embodied in Hendrickson (1991b) must be enforced prior to acceptance of wastes for disposal.

As described in §3.0, an assumption that the mean of all these waste streams would be represented by a mean of those reported is not considered appropriate. The reasons for this are that the original sources of the waste differ, and because the wastes would undergo differing treatment regimes. Table 1-4 of the Appendix details the data from Lowe (1991) and the evaluation of a mean as that described in Equation 3-1 with no volume weights assigned to zero.

In reiteration, this may introduce some non-conservative estimates for some analytes; however, it is believed that most analytes of potential concern in large streams are reported and form a valid basis of this family's estimate. The two lowest volume streams comprising 0.37% of the pretreated volumes to the HGDGP are least well described by Lowe

WHC-SD-WM-TI-528, Rev. 1

(1991); lack of explicit data on all aspects of these streams is considered insignificant.

3.4 Data Summarization and Interpretation

Data handling in §§3.1 through 3.3, above, resulted in the development of:

- a) An estimate of the composition of dilute wastes to be received [Appendix Table 1-1],
- b) An estimate of concentrated material to be produced in the future [Appendix Table 2-7],
- c) Estimates of all currently available concentrated feed [Appendix Tables 4-1, 4-2, and 4-3], and
- d) An estimate of all expected materials subject to pretreatment [Appendix Table 1-4].

In order to combine the above information and to determine an estimate of the overall inventory of materials to be received at the disposal facility, several aspects of process and data handling must be considered. These aspects include decay dates for radioactive materials, evaluation of requirements for dilute wastes, use and application of limiting values, and analytical errors. Each of these aspects and their impact on the estimate of overall inventory are described below.

3.4.1 Application of Uniform Decay Date

In order to combine analytical data on the radionuclide content of existent waste streams, a uniform decay date was selected. Unlike chemical constituents which will not significantly vary over time except through physical means, the radioactive components of the wastes continue to decrease in concentration through radioactive decay. The decay date chosen for this document has been that of October 1, 1993. This date has been chosen as it is the currently expected date of HGDP startup.

An example of the use and necessity of a uniform decay date in these calculations may be provided by describing the decay of ^{137}Cs in four existent concentrated waste tanks: 241-AN-103 and -106, 241-AW-101, and 241-AP-105. The analytical data is described within the Appendix tables as:

Tank	Sample Decay Date	^{137}Cs ($\mu\text{Ci/L}$)	Days before 10/01/93
241-AN-103	12/15/84	7.50 E+05	3,212
241-AP-105	01/30/89	2.85 E+05	1,705
241-AN-106	04/21/89	2.05 E+05	1,631
241-AW-101	07/17/90	5.20 E+05	1,172

WHC-SD-WM-TI-528, Rev. 1

The half-life of ^{137}Cs used within this document is 30.17 years (see Appendix Table 5-1 for other radionuclide data used). Conversion factors of 86,400 seconds per day and 31,556,736 seconds per sidereal year are used within decay equations (Hendrickson 1991a) to determine the activity of remaining material at some given time as:

$$\text{Activity}(t) = \text{Activity}(t_0) e^{\left(\frac{-\lambda t}{t_{1/2}}\right)} \quad [\text{Eq. 3.4}]$$

where: t = interval of decay, seconds
 λ = decay constant [$\ln(2) = 0.693$], and
 $t_{1/2}$ = isotope half-life, s.

For 241-AN-103 data, the uniform date activity may be evaluated as:

$$\begin{aligned} \text{Activity}(t) &= 7.5 \text{ E}+05 \text{ e}^{\left(\frac{-0.693 \cdot \left(3,212 \text{ days} \cdot \frac{86,400 \text{ s}}{\text{day}}\right)}{30.17 \text{ year} \cdot \left(\frac{31,556,736 \text{ s}}{\text{year}}\right)}\right)} \left(\frac{\mu\text{Ci}}{\text{L}}\right) \\ &= 6.128 \text{ E}+05 \left(\frac{\mu\text{Ci}}{\text{L}}\right) \quad [\text{Eq. 3.5}] \end{aligned}$$

In this manner, the decayed activities of ^{137}Cs are calculated as:

Tank	^{137}Cs Activity ($\mu\text{Ci/L}$)	
	Sample Data	Decayed Data to 10/01/93
241-AN-103	7.50 E+05	6.13 E+05
241-AP-105	2.85 E+05	2.56 E+05
241-AN-106	2.05 E+05	1.85 E+05
241-AW-101	5.20 E+05	4.83 E+05

In this fashion, and with the half-lives described in Appendix Table 5-1, all data which can be decayed are so calculated. Materials to be generated in the future are not decayed and are so marked.

3.4.2 Evaluation of Dilute Waste Requirements

Current waste acceptance criteria limit the radiolytic heat content of wastes to be disposed to the HGDGP. Radiolytic heat loading is a calculation of the heat released to the waste through high energy decay. Limits on such heat loading have been established to adequately protect the disposal system and product grout from excessive temperature during and after operational activities.

WHC-SD-WM-TI-528, Rev. 1

The unit established for the evaluation of heat loading of grout waste feeds is the heat provided by the decay of one curie of ^{137}Cs and its metastable daughter $^{137\text{m}}\text{Ba}$ [$^{137}\text{CsmBa}$]. Other high energy decay chains, of those expected in the wastes, are prorated and summed as described in Hendrickson (1991a) to yield a decay heat evaluation in terms of $^{137}\text{CsmBa}$ heat equivalents. The limiting acceptance value for radiolytic heat loading has been established as 0.3718 Ci $^{137}\text{CsmBa}$ heat equivalents/L (Hendrickson 1991b) at the time of disposal.

Observation of radiolytic heat loading of existent wastes [Appendix Table 1-3] calculated in this fashion, following decay as described in §3.4.1, demonstrates that some wastes would exceed the heat loading limit if disposed in their current form and concentration. Specifically, wastes contained in DST waste tanks 241-AW-101, 241-AN-103, -104, and -105 are each anticipated to exceed the heat loading limit. As such, these wastes must be blended with dilute wastes to reduce the overall radiolytic heat load.

Appendix Table 1-3 calculations yield the volumetric feed fraction (%) at which these wastes may be blended with dilute wastes to yield a mixture at the heat loading limit. Direct calculations of required dilute waste volume and their summation result in the determination that approximately nine million liters (2.39×10^6 gallons) of dilute waste are required. The composition of these dilute wastes are discussed in §§2.1 and 2.2 and tabulated in Appendix Table 1-1. The volume and composition of these required dilute wastes are carried throughout subsequent calculations.

3.4.3 Use and Application of Limiting Values

All laboratory analyses have some limit of detection and quantitation. When the concentration of a constituent is below the limit of the method, the analytical value typically reported is the detection or quantitation limit value. Such data is tagged as a "less-than" value. Examples of such "less-than" results are contained within Appendix Tables 2-1 through 2-6 and 3-1 through 3-5. Where such "less-than" data are used within this document, they are acted upon and weighed with other analyses as if they were indeed real values.

This application of limiting values of detection and quantitation as real values is inherently conservative and has the unfortunate side effect of eliminating any estimate of analytical variability (e.g. see Welsh 1991a and 1991b). Thus, despite this shortfall in general statistical validity, it is considered the only reasonable way to handle this data directly while developing generalized inventory estimates.

In keeping with the application of "less-than" values as real values, summary tables (Table 4 and Appendix Tables 1-1, 1-2, 1-4 and 4-1 through 4-3) of this document no longer carry the "less-than" indicators. As is applied in §4.0, the existence and validity of the use of "less-than" values for a constituent may be investigated when the waste constituent is of significant importance.

WHC-SD-WM-TI-528, Rev. 1

3.4.4 Analytical Errors

Data used within this evaluation include a broad range of qualified and unqualified data. Errors inherent within any analytical report include those of sampling error as well as random and systematic measurement error.

Analytical summaries, such as those prepared for waste tanks 241-AN-106 and 241-AW-101 (Welsh 1991a and 1991b) have addressed the lack of significant effect of sampling error upon well characterized tanks when those tanks are considered homogenous. In this perspective, reported mean concentrations are considered adequate and often carry standard deviations of approximately 10% to 17%. The overall variance is composed of both sampling and measurement error.

For many data sources used within this document, it is not possible at this time to easily determine whether such analyses were conducted in duplicate, nor whether blanks, matrix spikes and other qualification methods were employed in data generation. Thus, the only available estimates of error on such reports are those of analytical measurement error.

The overall analytical measurement error is composed of two variance components. The first is known as the systematic error variance (S_s^2) and the second is the random error variance (S_r^2). The combined estimate of variance is:

$$S^2 = S_s^2 + \frac{S_r^2}{n} \quad [Eq.3.6]$$

where n is the number of measurements used to estimate the concentration (the analytical measurement). The systematic error variance is usually estimated through the use of known standards. Examples of laboratory standard errors include percent standard deviations (one standard deviation) of 10.96% for ^{99}Tc at an activity near 2 $\mu\text{Ci/L}$ and 17.16% for ^{129}I at an activity near 1 $\mu\text{Ci/L}$. For Westinghouse Hanford Company the laboratory standard results are reported and stored in the LMCS database. The random error variance is usually estimated from the duplicate sample results.

Estimates of these errors, in terms of standard deviation or relative standard deviation, have been computed based on analytical results from samples obtained from Tanks 241-SY-101, 241-AN-106, and 241-AW-101 (Herting et al. 1992; Welsh 1991a and 1992b). Standard deviation is the square root of the variance. The error estimates based on Tank 241-SY-101 sample data (Window E) are found in Tables 7.5, 7.6, and 7.10 in Herting et al. (1992). Although not directly specified, the magnitude of the random error component based on sample data from Tank 241-AN-106, can be obtained from the percent difference data (%Diff.) given in Appendix C of Welsh (1991a). The random error estimates based on Tank 241-AW-101 are found in Table 4 of Welsh (1991b).

WHC-SD-WM-TI-528, Rev. 1

For those analytes which are reported as "less than" values, the random analytical error can also be estimated from the analysis of laboratory standards.

The overall tank concentration error is a function of the analytical measurement error and the "degree" of homogeneity within the tank. If the tank is homogeneous, then the overall error is mainly comprised of the analytical error. The random variability within Tank 241-AW-101, which is estimated by the relative standard deviation [RSD] (standard deviation divided by the mean multiplied by 100), can be computed from Table 6 of Welsh (1991b). However, the random error (in terms of RSD) for the overall mean would be the $RSD/\sqrt{n}$. The random variability within Tank 241-AN-106, which is estimated by the relative standard deviation, can be computed from Table 6 of Welsh (1991a). The random error (in terms of RSD) for the overall mean would be the $RSD/\sqrt{n}$. Tank 241-AN-106 is known to be a stratified tank (not homogenous). Thus the within tank variability should be larger than the within tank variability of Tank 241-AW-101.

Overall analytical errors described above are expected to yield standard deviations about data in the region of 10% to 20%. Although sensitivity analyses may apply such error ranges about data in evaluating the environmental impact of waste constituents in the disposal action, the evaluation of a best estimate of overall inventory precludes direct application within this document.

3.4.5 Data Summary

The two basic groups of wastes, the "DSSF Family" and pretreatment family, remain substantially different in source and handling. Thus, the combination of these materials in this evaluation is conducted as the last action.

3.4.5.1 DSSF Family Waste Summary

The DSSF Family waste contribution to the HGDP waste feed projections is a combination of existent concentrated wastes, future concentrated wastes, and dilute wastes. The combination of these materials may be gathered and easily expressed.

Armed with the estimate of diluent waste volume required (§3.4.2), the DSSF family of wastes is collected on Appendix Table 1-2. This table shows the translation from the previous calculations of waste composition, such that each existent concentrated waste is decayed to the uniform decay date of October 1, 1993, by applying Equation 3.4. Dilute wastes and future concentrated wastes are not decayed. A summary of the DSSF family is calculated and presented on Appendix Table 1-2 in the manner of Equation 3.1. This summary is passed forward and presented as the first data column of Table 4.

WHC-SD-WM-TI-528, Rev. 1

3.4.5.2 Grout Waste Feed Projection Summary

A final combination of DSSF family wastes and pretreated wastes is performed in the method of Equation 3.1. Just as the dilute and future concentrated wastes were not decayed to form Appendix Table 1-2, above, pretreated waste composition is not decayed. This is not considered a significant error in that the time of generation of these wastes is not yet known, and as the pretreatment regimes through which this material will pass are expected to remove the majority of intermediate-lived radionuclides (e.g. ¹³⁷Cesium) and may remove a majority of the long-lived transuranic material.

The resultant composition estimate is provided in Table 4. It must be noted that the third data column (Total Feed) of Table 4 is equivalent to that concentration for an analyte if that analyte is described in only one of the major streams. This is considered a conservative yet necessary assumption when no analysis for the analyte is available.

Certain radionuclides are considered sensitive enough, from a long-term release standpoint, that refinement or affirmation of an estimate contained in Table 4 is warranted. These "special estimates" are described in §4.0 and yield Table 8 which overrides some estimates described in Table 4.

3.5 Recommendations on Data Usage

It is recommended that the information provided herein, when used in summary form, be segmented by the two waste families described. As described in §3.3, fewer analytes are described for two low volume pretreatment streams, errors introduced from the lack of completeness of the preliminary pretreatment flowsheets is not expected to be significant with regard to these low volume streams.

It is recommended that more complete data be developed to accurately estimate the projected volume and concentration profile of future wastes, and that information provided herein as estimates be replaced with actual sample data when such becomes available. Of particular note, high ²⁴¹Americium data reported for Evaporator campaign 84-3, if representative, may prohibit (Hendrickson 1991b) the disposal of the DSSF wastes in tanks 241-AN-104 and 241-AN-105 without pretreatment.

Information acquisition on these, and other, tank wastes is often complicated by extensive safety precautions. Such precautions, and the development of documentation for such, may effectively prohibit significant information acquisition on these wastes in the near future.

Speciated organic chemical analysis has not been within the analytical compass of the majority of wastes described in this document, and as such, has been omitted herein. Although not described in this document, such analysis must be conducted to ensure that waste feeds remain acceptable for disposal (Hendrickson 1991b).

WHC-SD-WM-TI-528, Rev. 1

With the above considerations, the estimates provided within this document are considered to be the most current and complete estimate of waste feed materials to the Hanford Grout Disposal Program and may be used as a guide in regulatory compliance, general flowsheet, and performance assessment activities wherein an order of magnitude accuracy is required. This document, as it describes an average of the inherent differences between waste streams should not be construed to override single stream data for safety analyses or design especially when new data on each waste stream is acquired.

WHC-SD-WM-TI-528, Rev. 1

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Ag	8.90 E-05	4.08 E-05	6.48 E-05
Al	4.92 E-01	4.05 E-01	4.48 E-01
As	2.00 E-04	1.97 E-04	1.99 E-04
B		3.37 E-03	3.37 E-03
Ba	4.66 E-05	1.18 E-04	8.22 E-05
Be	1.78 E-03		1.78 E-03
Bi	3.13 E-04		3.13 E-04
Ca	1.00 E-03	7.30 E-03	4.16 E-03
Cd	6.45 E-05	1.60 E-04	1.12 E-04
Ce		1.44 E-04	1.44 E-04
Cr	4.23 E-03	1.92 E-02	1.18 E-02
Cu	1.49 E-04	4.08 E-04	2.79 E-04
Fe	1.78 E-03	1.85 E-02	1.01 E-02
Hg	5.49 E-06		5.49 E-06
K	3.44 E-01	5.65 E-02	2.00 E-01
La		1.15 E-04	1.15 E-04
Li		6.81 E-05	6.81 E-05
Mg	1.62 E-03	4.05 E-03	2.83 E-03
Mn	2.62 E-04	7.03 E-03	3.66 E-03
Mo	4.24 E-04	8.54 E-04	6.40 E-04
Na	6.00 E+00	5.00 E+00	5.50 E+00

Decay Date = 10/01/93
3-18

WHC-SD-WM-TI-528, Rev. 1

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Nd		1.20 E-04	1.20 E-04
Ni	6.22 E-04	1.89 E-03	1.26 E-03
P	4.98 E-02		4.98 E-02
Pb	5.37 E-04	1.19 E-04	3.27 E-04
Sb	1.31 E-03	6.13 E-05	6.86 E-04
Se	1.75 E-04	6.13 E-04	3.95 E-04
Si	3.38 E-03	8.77 E-03	6.08 E-03
Ta	1.36 E-05		1.36 E-05
Ti	9.14 E-05	9.95 E-05	9.55 E-05
U (g/L)	2.11 E-02	4.24 E-01	2.23 E-01
V	3.14 E-04		3.14 E-04
W	1.13 E-03		1.13 E-03
Zn	1.66 E-03	4.08 E-04	1.03 E-03
Zr	2.50 E-04	5.09 E-02	2.56 E-02
CN ⁻	4.01 E-04		4.01 E-04
NH ₃	6.88 E-03	3.99 E-03	5.43 E-03
CO ₃ ⁻²	2.12 E-01	1.12 E-02	1.11 E-01
Cl ⁻	9.24 E-02	5.51 E-02	7.37 E-02
F ⁻	6.11 E-01	3.95 E-01	5.02 E-01
SO ₄ ⁻²	7.63 E-02	6.70 E-02	7.16 E-02
NO ₃ ⁻	1.74 E+00	3.76 E+00	2.75 E+00

Decay Date = 10/01/93
 3-19

WHC-SD-WM-TI-528, Rev. 1

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
NO_2^-	9.37 E-01	7.42 E-02	5.04 E-01
PO_4^{3-}	2.69 E-02	3.46 E-02	3.07 E-02
OH^-	2.15 E+00	1.55 E-01	1.15 E+00
TOC (g/L)	8.15 E+00	3.54 E-03	4.07 E+00
TIC (g/L)	5.19 E+00		5.19 E+00
SPG	1.29 E+00		1.29 E+00
pH	1.35 E+01		1.35 E+01
^3H	5.12 E+00		5.12 E+00
^{14}C	2.85 E-01	3.71 E+00	2.00 E+00
^{60}Co	3.91 E+01	1.56 E+01	2.73 E+01
^{63}Ni		1.19 E+02	1.19 E+02
^{79}Se	3.00 E+00		3.00 E+00
^{90}Sr	1.82 E+03	2.39 E+04	1.29 E+04
^{94}Nb	4.33 E+01		4.33 E+01
^{95}Nb	5.34 E+01	3.49 E+03	1.78 E+03
^{99}Tc	4.87 E+01	5.47 E+01	5.17 E+01
^{103}Ru	1.29 E+02		1.29 E+02
$^{106}\text{RuRh}$	1.62 E+03	2.07 E+03	1.84 E+03
^{113}Sn	1.78 E+02		1.78 E+02
^{129}I	2.18 E-01	2.61 E-02	1.22 E-01
^{134}Cs	5.76 E+02	6.21 E+01	3.18 E+02

Decay Date = 10/01/93
 3-20

WHC-SD-WM-TI-528, Rev. 1

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
^{137}Cs	2.27 E+05	3.67 E+04	1.32 E+05
$^{144}\text{CePr}$	9.80 E+02	2.12 E+03	1.55 E+03
^{154}Eu	1.47 E+02	4.79 E+01	9.73 E+01
^{155}Eu	2.85 E+02	4.91 E+01	1.67 E+02
^{226}Ra	1.32 E+03		1.32 E+03
^{234}U	4.45 E-02		4.45 E-02
^{235}U	2.71 E-03		2.71 E-03
^{238}U	1.04 E-02		1.04 E-02
^{237}Np	8.81 E-01	2.90 E-04	4.39 E-01
^{238}Pu	2.23 E-01	9.41 E-02	1.59 E-01
$^{239/240}\text{Pu}$	2.09 E+00	3.08 E+00	2.59 E+00
^{241}Am	1.35 E+03	2.78 E+01	6.86 E+02
^{243}Cm	4.14 E-02		4.14 E-02
^{244}Cm	8.92 E-02	1.65 E-02	5.28 E-02
TB	1.56 E+04		1.56 E+04
AT	1.86 E+00		1.86 E+00
Volume (L)	6.08 E+07	6.12 E+07	1.22 E+08

Decay Date = 10/01/93
 3-21

WHC-SD-WM-TI-528, Rev. 1

TABLE 4: Grout Treatment Facility Waste Projection (Units: $\mu\text{Ci/L}$ for radionuclides, molarity for others unless noted)			
Waste Component	DSSF Family	Pretreated Wastes	Total Feed
Additional analytes described for pretreated wastes			
^{95}Zr		1.73 E+03	1.73 E+03
^{125}Sb		5.41 E+02	5.41 E+02
^{152}Eu		4.08 E+00	4.08 E+00
^{241}Pu		8.90 E+00	8.90 E+00
^{242}Pu		1.57 E-05	1.57 E-05

Decay Date = 10/01/93
3-22

WHC-SD-WM-TI-528, Rev. 1

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1

4.0 SPECIAL ESTIMATES OF CRITICAL ISOTOPES

As described in §3.5, it is recommended that further analytical data be developed for the projection of grout waste estimates. Such additional data will not come rapidly nor inexpensively. In the meantime, however, waste material estimates derived above may either overestimate, underestimate or fail to address waste constituents critical to an assessment of the human and environmental protection afforded by the proposed disposal action (Performance Assessment).

In consideration of this, one may turn to methods other than direct waste analysis in order to evaluate whether such an assessment should consider application of constituent concentrations differing from those described in Table 4.

The purpose of this section is to consider, describe, and apply other methods of waste constituent estimation and to provide recommendations regarding waste constituents currently believed to be potentially critical in evaluation of the proposed disposal action. Sections 4.1 through 4.10 develop estimates and recommendations for waste constituents including ^{241}Am , ^{238}U , ^{237}Np , ^{230}Th , ^{226}Ra , ^{135}Cs , ^{129}I , ^{126}Sn , ^{99}Tc , ^{94}Nb , ^{79}Se , and ^{14}C . Section 4.11 summarizes and tabulates these estimates and recommendations.

Although it may be expected that ^{137}Cs and ^{90}Sr will play a major role in the assessment of disposal actions, estimates based on other than analytical data are not pursued in this section because these materials are routine waste analytes; as such, it is considered inappropriate to override analytical measurements with mathematical estimates.

4.1 $^{135}\text{Cesium}$ Estimation

Cesium-135 is not a routine analyte in waste analyses and is not represented in Table 4. The reasons for this are several and include incapability to chemically separate ^{135}Cs from ^{134}Cs and ^{137}Cs and a half-life five orders-of-magnitude [OM] greater than that of ^{137}Cs and six OM greater than that of ^{134}Cs .

The approach used herein to estimate ^{135}Cs content of wastes to be received at the HGDP is to apply data from the burnup of fuel with results in the form of ^{135}Cs and ^{137}Cs content from which a ratio of production may be made.

Hedengren (1985, 1986) and Hedengren and Goldberg (1987) have conducted calculations using the ORIGEN2 code to determine expectations of fission, actinide, cladding, and activation products from the irradiation of fuel under various conditions. Table 5 contains excerpts of data from these references as they apply to calculations within §4. of this document. The product data of Table 5 derive from ORIGEN2 runs assuming a 12% (^{240}Pu /total Pu) product using mixed Mark IV (80%) and Mark IA (20%) N Reactor fuel. Some benchmarking of ORIGEN2 for N reactor operations has been conducted but the code has not completed verification and validation. Despite

WHC-SD-WM-TI-528, Rev. 1

the unvalidated status of this code, it and its results are used within this document as they are expected to be approximately correct and because they provide the only reasonable nonclassified production estimate available at this time.

TABLE 5: ORIGEN2 Yield Per Metric Ton of Fuel (Ci) [For 12% Pu Mixed Mark IV and Mark IA Fuel Five Years After Discharge]				
Isotope	Fuel Fission Product	Fuel Actinide Product	Cladding and Fuel Activation Product	Specific Activity (Ci/g)
¹⁴ C	1.024 E-05		2.023 E-02	4.46 E+00
⁷⁹ Se	3.757 E-02			6.96 E-02
⁹⁴ Nb	9.158 E-06		6.093 E-08	1.90 E-01
⁹⁹ Tc	1.259 E+00		1.736 E-06	1.70 E-02
¹²⁶ Sn	6.490 E-02			2.84 E-02
¹²⁹ I	2.709 E-03			1.76 E-04
¹³⁵ Cs	3.356 E-02			1.15 E-03
¹³⁷ Cs	8.184 E+03			8.65 E+01
²²⁶ Ra (W)		7.978 E-10		9.89 E-01
²³⁰ Th		2.201 E-05		2.06 E-02
²³⁷ Np		2.729 E-02		7.05 E-04
²³⁸ U		3.319 E-01		3.36 E-07
²⁴¹ Am		5.320 E+01		3.43 E+00
²⁴¹ Pu		5.655 E+03		1.03 E+02

Note: Specific Activities derived from Walker et al. (1989).
²²⁶Ra production in terms of watts (W).

As can be seen in Table 5, 0.03356 Ci of ¹³⁵Cs is produced for every 8,184 Ci of ¹³⁷Cs. Similar production ratios of other materials will be applied below.

4.1.1 Back-Decay of ¹³⁷Cesium Data

In order to apply the relative data given above, an estimate for ¹³⁷Cs is required. The estimate of cesium-137 production can be calculated from analysis at any date after production given the half-life of the material. Thus, where Table 1-2 of the Appendix contains ¹³⁷Cs data decayed to October 1, 1993, each of these analyses may be back-decayed to an estimated time of material separation.

WHC-SD-WM-TI-528, Rev. 1

For purposes of uniformity, the time of fuel discharge is assumed to be October 1, 1977, and fuel processed in PUREX on October 1, 1982. This period of five years between fuel discharge and processing (fuel "cooling" period) is assumed to be a slightly conservative and typical interval necessary in these and later calculations involving the ingrowth of radioisotopes. Fuel cooling periods of five years have been assumed in subsequent calculations to compensate for the ingrowth of radioactive isotopes; these may be significant when the parent radionuclide is present in high concentration in the irradiated fuel (e.g. ^{230}Th ingrowth from alpha decay of ^{234}U).

Although not all of the wastes described here were processed, sampled, or concentrated by the above dates, they provide a reasonable average fuel discharge date, and consequent initial generation and decay of cesium-137. Applying a half-life of 30.17 years and a decay time of 11 years to the ^{137}Cs data on Appendix Table 1-2 results in cesium activities, at that time, of 20.7 million curies. Details of this calculation are provided in Table 6, below.

It should be noted that close agreement between ^{137}Cs estimates may be found between that provided above and through the Integrated Data Base (DOE 1991 [Table 2-17]) (IDB). Back-decay of IDB data to October 1982 would yield ^{137}Cs activity in tanks to be 21.1×10^6 Ci.

4.1.2 $^{135}\text{Cesium}$ Production

The estimate of ^{135}Cs production may be made as the ORIGEN2 ratio of ^{135}Cs production to ^{137}Cs production times the analytical estimate of production five years after discharge of ^{137}Cs and computed as:

$$\begin{aligned} \text{Cs-135 (Ci)} &= \frac{0.03356 \text{ Ci Cs-135}}{8,184 \text{ Ci Cs-137}} * 20,663,000 \text{ Ci Cs-137 [Eq. 4.1]} \\ &= 84.73 \text{ Ci Cs-135} \end{aligned}$$

For the purposes of the Performance Assessment, correction of this activity through decay to current values is insignificant (>99.9996% remaining in 1993) and thereby neglected.

WHC-SD-WM-TI-528, Rev. 1

TABLE 6: Waste ¹³⁷ Cs Activity [Decay Date 10/1/1982]			
Tank	Cs-137 (Ci/L)	Volume (L)	Cs-137 (Ci)
106-AN	0.238	3,667,985	874,094
101-AW	0.622	3,826,969	2,378,645
105-AP	0.329	3,145,609	1,035,247
104-AN	0.973	3,024,479	2,941,880
105-AN	0.649	4,269,852	2,772,392
103-AN	0.789	3,546,854	2,798,393
Future DDSSF	0.156	30,282,640	4,713,889
Dilutes	0.02863	9,045,555	259,001
Pretreated	0.0472	61,164,750	2,889,253
Total		121,974,693	20,662,794

4.1.3 ¹³⁵Cesium Estimate Usage

The estimate of ¹³⁵Cs production given above as 84.7 Ci is greater than the reported current activity of 59.2 Ci within the IDB (DOE 1991 [Table 2-17]). Waste content of ¹³⁵Cs is not described within the HDW-EIS. At this time, no information has been identified which would suggest that ¹³⁵Cs has been preferentially separated from ¹³⁷Cs in any Site operations (chemically identical); thus reduction of either of these two estimates by any referencable factor is not reasonable.

In reference to the two estimates derived or given above, it is recommended that grouted waste inventory calculations use a base case not exceeding a maximum ¹³⁵Cs concentration applying the ORIGEN2 and analytically derived estimate of 0.695 μ Ci/L. Sensitivity analyses may be pursued of 0.485 μ Ci/L corresponding to IDB estimates of site inventory.

4.2 ²³⁷Neptunium Estimation

An improved estimate of ²³⁷Np is sought in this section due to the minimal data provided in reference information. Further complicating this estimate is the ingrowth of ²³⁷Np from the alpha decay of ²⁴¹Am. This ingrowth is not explicitly incorporated in the transport and dose codes to be used in performance assessments, but the input may be manipulated to account for the ingrowth of the americium as its half-life is only 432.7 years compared to the neptunium half-life of 2.14 million years.

WHC-SD-WM-TI-528, Rev. 1

4.2.1 Revision of ^{241}Am Estimates

The americium contained within the waste streams is the result of neutron bombardment of fuel and the ingrowth from beta-decay of ^{241}Pu . Under the conditions of burnup described in §4.1, Hedengren and Goldberg (1987, page I17), provide a five year post-discharge yield of 53.2 Ci ^{241}Am per metric ton of fuel. Using a calculation in the form of Equation 4.1, ^{241}Am content of wastes decayed to October 1993, would be 131,972 Ci. The IDB estimate of ^{241}Am in all Hanford Double-Shell wastes decayed to October 1993 is 52,253 Ci (DOE 1991).

The difficulty remains with estimation of realistic activities of the wastes. As can be seen in Appendix Tables 3-1 through 3-5, 4-3, and 1-2, the overall "DSSF Family" americium estimate of Table 4 is driven by one sample analysis from Evaporator Campaign 84-3 (Certa 1985). If this analytical value of 11,400 $\mu\text{Ci/L}$ accurately represents both tanks 241-AN-104 and 241-AN-105, the americium content of these tanks would be 83,155 Ci; clearly this activity, in excess of IDB estimates, is not reasonable. If the analytical value represented only that portion of 241-AN-104 which has above been attributed from Campaign 84-3, this portion of material would include 6,408 Ci of ^{241}Am . This is a possible, but not highly realistic value.

Omitting the analytical americium datum of Campaign 84-3, no data is available to consider for DSSF tanks 241-AN-104 and 241-AN-105. In the overall manner of this document, the preferred method of estimation should be that of bridging a data gap. Data may be bridged in this instance by choosing a maxima or by interpolation based upon other parameters, such as is depicted in Figure 3 of §3.0. Data does remain for other DSSF wastes, and may form a basis for revising the estimate.

4.2.1.1 TRU Limitation in DSSF Waste

Waste feeds to the HGDP are limited by regulatory requirements to a maximum of 100 nanocuries of transuranic (TRU) material per gram of waste (Hendrickson 1991b). Given the density of wastes contained within tanks 241-AN-104 and 241-AN-105, a maximum ^{241}Am concentration within these wastes is 153 $\mu\text{Ci/L}$. Use of such a concentration is acceptable as a bounding value as these wastes would require pretreatment for TRU removal were they any higher. The use of this concentration is a factor of almost seventy-five above the analytically reported values (see §4.2.1 and Appendix Table 1-2) of other DSSF wastes.

A summary of the estimate of overall ^{241}Am to be received by the HGDP under the assumption that 241-AN-104 and -105 are at their TRU limits is contained in Table 7. These sources are ranked by expected contribution. It should be noted that the volumes described in Table 7 do not exactly equal those of Table 6 as no americium estimate for NCAW pretreatment streams 13 are provided in Lowe (1991); differences due to these small volume streams (0.37% of pretreatment volumes) are neglected in further calculations of this section.

WHC-SD-WM-TI-528, Rev. 1

TABLE 7: ²⁴¹Americium Sources [Decay Date 10/01/82]

Source	Am-241 (Ci/L)	Volume (L)	Am-241 (Ci)	Mean (Ci/L)
NCAW 2AZ	3.20 E-04	3.50 E+06	1,118.53	
DSSF (4AN/5AN Max.)	1.53 E-04	7.29 E+06	1,114.99	
PFP	1.76 E-04	2.08 E+06	366.29	
CC	3.05 E-06	3.90 E+07	119.08	
NCAW 1AZ	3.39 E-05	3.49 E+06	118.28	
DDSSF	8.96 E-07	3.03 E+07	27.14	
DSS/DSSF (not 4AN/5AN)	1.37 E-06	1.42 E+07	19.37	
NCRW 5AW	8.63 E-07	5.30 E+06	4.57	
Dilutes	1.18 E-07	9.05 E+06	1.07	
NCRW 3AW	9.96 E-08	7.57 E+06	0.75	
Total		1.22 E+08	2,890.07	2.374 E-05
Decayed to 10/01/93				2.33 E-05

Note: This assumes that tanks 241-AN-104 and -105 are bounded in ²⁴¹Am content at 100 nCi/g. NCAW 2AZ concentration believed to be erroneously high.

Relative contributions of ²⁴¹Am from projected waste feeds for this assumption are depicted in Figure 4. This image emphasizes the expectation that the vast majority (>98%) of ²⁴¹Am to be received in HGDW wastes is to be contained in pretreated waste streams and assumed maxima within DSSF tanks 241-AN-104 and 241-AN-105. Such an estimate, in conjunction with the impacts of near-surface disposal of this material, may be the basis for extended pretreatment to remove additional transuranic material.

4.2.1.2 Concentration Factor Evaluation in DSSF Waste

Although a conservative bound for ²⁴¹Am content may be found in §4.2.1.1, it is possible to use the observations depicted in Figure 3 to arrive at an estimate of ²⁴¹Am content in tanks 241-AN-104 and -105. Those concentrated waste tanks for which reasonable americium data are available include tanks 241-AN-106, 241-AW-101, 241-AN-103, and an estimate based on processing of 241-AP-105. The temporary exclusion of dilute, future concentrate, and pretreated wastes is necessary for this estimate as will be evident below.

WHC-SD-WM-TI-528, Rev. 1

Figure 4: Distribution of Am-241 Sources to Grout (Assumes maximum allowable in 4AN/5AN)

Back-decay of ^{241}Am data for these four concentrated waste tanks to 1982 and comparing these data to waste sodium content, in the manner of Figure 3, provides a linear regression characterized by Equation 4.2 with a correlation coefficient of nearly 92%. This is considered a good fit and may allow global estimation of ^{241}Am content based upon sodium content. Applying waste volumes and sodium concentrations of the existent concentrated DSSF family wastes, one arrives at a weighted mean sodium molarity of 9.87 mol/L.

$$\text{Am-241 } (\mu\text{Ci/L}) = 0.13867 * \text{Na (M)} + 0.16508 \quad [\text{Eq. 4.2}]$$

Applying this sodium concentration to Equation 4.2 yields a mean estimate of 1.533 $\mu\text{Ci } ^{241}\text{Am/L}$ for these 21.48 million liters (32.93 Ci). Continued calculation in the manner of Table 7 results in an overall estimated concentration of 14.4 $\mu\text{Ci/L}$.

As described above, dilute and future concentrate wastes were not considered in the linear regression. The basis of this exclusion is that analytical data on those wastes do not support the above

WHC-SD-WM-TI-528, Rev. 1

regression; in fact, Equation 4.2 would predict approximately twice as much americium than has been analytically reported in the dilute wastes.

It is postulated that previous americium and cesium sources in the waste streams to the DSTs have slowly decreased in content of these materials with serial facility shutdowns. In this respect, the analytical estimates for dilute and future concentrates as described above will be conservative.

Pretreated waste streams should not follow Equation 4.2 as it is the express intent of such pretreatment to remove transuranic material. Thus, the flowsheets (Lowe 1991) continue to provide the appropriate estimation basis for these wastes.

4.2.1.3 Usage of ^{241}Am Estimates

Revised estimates of americium content of HGDP waste feeds in §§4.2.1.1 have resulted in an expectation of a mean ^{241}Am content of 23.32 $\mu\text{Ci/L}$ [decay date 10/01/93] over all wastes. This estimate is recommended as a base case when applying such data. Three sensitivity case evaluations, each decayed to 10/01/93, of americium content beyond the base case are most well supported as:

- Case I: Linear regression of americium data relative to sodium content (Eq. 4-2) to describe existent concentrated DSSF Family wastes while using remainder of base case; 1,758.0 Ci (14.4 $\mu\text{Ci/L}$), and
- Case II: IDB basis; 52,253 Ci (428.4 $\mu\text{Ci/L}$).
- Case III: Production and decay, related to waste ^{137}Cs content [analogous to Eq. 4.1] for DSSF Family wastes plus pretreated waste estimate; 131,972 Ci (1,082 $\mu\text{Ci/L}$).

A case for estimation based on IDB less that pretreated material to be shipped to the Hanford Waste Vittrification Project is untenable as the pretreatment flowsheet estimates (Lowe 1991) of material fed to pretreatment exceed ^{241}Am estimates of the IDB by greater than one OM. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated 17,000 Ci of ^{241}Am in near-surface barriered disposal; this activity, in view of the span of the above cases, is sufficiently close to those cases that establishment of an another case for this estimate is not considered necessary.

4.2.2 Revision of ^{237}Np Estimates

As described above, the neptunium contained within the waste streams is the result of bombardment of fuel (^{235}U & ^{236}U & ^{237}U & ^{237}Np) and the ingrowth from decay of ^{241}Pu and ^{241}Am . Under the conditions of burnup described in §4.1, Hedengren and Goldberg (1987 pages I15 and I17), provide yields of 5,655 Ci ^{241}Pu (54.9 g), 53.2 Ci ^{241}Am (15.5 g), and 0.02729 Ci ^{237}Np (38.7 g) per metric ton of fuel five years after discharge.

WHC-SD-WM-TI-528, Rev. 1

4.2.2.1 Production Estimation of ^{237}Np

As described above, it is obvious that a calculation in the form of Equation 4.1 and subsequent decay would yield an inordinately large estimate of the neptunium and americium decay daughters of the plutonium. More simply, this type of relationship would not be appropriate as the plutonium has been extracted in fuel processing. Fractional retention of ^{241}Pu in the waste stream yields a negligible difference in the ^{237}Np content as a result of decay, thus an approximation of complete ^{241}Pu removal in fuel processing may be used. In the manner of Equation 4.1, a production estimate of ^{237}Np would be 68.90 Ci which, with additional decay from ^{241}Am (assuming 100% yield of ^{237}Np), would yield a 1993 estimate of 68.91 Ci ^{237}Np .

4.2.2.2 Usage of ^{237}Np Estimates

A revised estimate, based on production, of neptunium content of HGDP waste feeds in §4.2.2.1, would result in the expectation of a mean ^{237}Np content of 0.565 $\mu\text{Ci/L}$. The IDB estimate of 45.1 Ci, would yield a mean of 0.37 $\mu\text{Ci } ^{237}\text{Np/L}$. As presented in Table 4, an analytically based estimate of content would be 53.6 Ci with a mean concentration of 0.439 $\mu\text{Ci/L}$.

It is recommended that the base case of waste evaluation, when such is applied in long term dose assessments, remain that provided in Table 4. Two sensitivity cases, one of lower activity and one higher, may be supported with the IDB estimate and the expected production (§4.2.2.1) estimate, respectively. As each of these sensitivity cases is within a factor of two of the recommended base case, it is noted that inaccuracies or differences in transport modeling may obviate any long term dose sensitivity due to such a minor variance in waste activity.

4.3 $^{226}\text{Radium}$ Estimation

Radium-226 is produced within irradiated fuel and is a daughter of $^{230}\text{thorium}$. Its radioactive daughters follow the decay chain of $^{226}\text{Ra} \rightarrow ^{222}\text{Rn} \rightarrow ^{218}\text{Po} \rightarrow ^{214}\text{Pb} \rightarrow ^{214}\text{Bi} \rightarrow ^{214}\text{Po} \rightarrow ^{210}\text{Pb} \rightarrow ^{210}\text{Bi} \rightarrow ^{210}\text{Po} \rightarrow ^{206}\text{Pb}$ (stable), where the decays between, and following, radon and lead-210 are rapid. Lead-210 is unstable but has a much greater half-life than the intermediate daughters. A better estimate of the content of ^{226}Ra in the waste is required as significant quantities of ^{226}Ra may result in large dose consequences due to the decay of it and its daughters over the period of the Performance Assessment.

The estimate of ^{226}Ra given in Table 4 is derived from analyses of current dilute waste tanks (see §3.1.1). Data reported from these wastes are "less-than" values (see Appendix Tables 2-1 through 2-6) resulting in an extrapolated DSSF Family concentration of 1,325 $\mu\text{Ci/L}$. Such an estimate would indicate expected disposal of 80,552 Ci of ^{226}Ra in DSSF Family wastes. This large estimate is not consistent with the absence of discussion of this isotope within the IDB and the HDW-EIS.

WHC-SD-WM-TI-528, Rev. 1

Lacking any other analytical data on this isotope, the waste content may again be approximated in the manner of §4.1.2, based upon production. Hedengren and Goldberg (1987) encompass the production of ^{226}Ra within fuel irradiation. However, due to the necessity to limit the publication of what was felt to be extraneous data (many zeros would be displayed and printed in the document if a limiter had not been applied) ^{226}Ra data is only displayed within tables of thermal power rather than directly in tables of mass or activity. Table I9 (Hedengren and Goldberg 1987, page I20) provides the thermal power of ^{226}Ra five years after discharge to be 7.978×10^{-10} watts. Browne et al. (1986) provide the delta of the alpha decay of ^{226}Ra to ^{222}Rn to be approximately 4.77 Mev/dis. Thus, the thermal power at that time may be calculated in terms of activity as:

$$Q\left(\frac{W}{Ci}\right) = \frac{4.77 \text{ Mev}}{\text{dis}} \times \frac{1.60219E-06 \text{ erg}}{\text{Mev}} \times \frac{1E-07 \text{ Ws}}{\text{erg}} \times \left(\frac{3.70E+10 \text{ dis}}{s} \right) \left[\text{Eq. 4.3} \right]$$

$$= 2.8277E-02 \left(\frac{W}{Ci} \right)$$

$$\text{Ra-226} \left(\frac{Ci}{\text{tonne}} \right) = \left(\frac{\frac{7.978E-10 \text{ W}}{\text{tonne}}}{\frac{2.828E-02 \text{ W}}{Ci}} \right) = 2.82 E-08 \left(\frac{Ci}{\text{tonne}} \right) \quad [\text{Eq. 4.4}]$$

$$\begin{aligned} \text{Ra-226 (Ci)} &= \frac{2.82E-08 \text{ Ci Ra-226}}{8,184 \text{ Ci Cs-137}} * 140,280,000 \text{ Ci Cs-137} \quad [\text{Eq. 4.5}] \\ &= 4.84 E-04 \text{ Ci Ra-226} \end{aligned}$$

Note that the ^{137}Cs value of Equation 4.5 is not that developed for and used in Equation 4.1. This higher ^{137}Cs number is derived from two sources in addition to that activity described in Table 6. The use of this higher value is in part due to the acknowledgement that lack of data on pretreatment flowsheets does not indicate the absence of a waste component. Explicitly, waste sources have or will have ^{137}Cs removed from the streams in processes which do not effect the removal of other analytes.

Pretreated waste streams may be corrected for ^{137}Cs content as an 11 year back-decayed ^{137}Cs estimate of material fed to pretreatment operations (Lowe 1991), thereby replacing the pretreated activity of 2.25 million curies of Table 6 with 46.41 million curies.

WHC-SD-WM-TI-528, Rev. 1

Both pretreated wastes and general DST contents may be corrected due to cesium scavenging in B Plant operations based upon cesium capsule content. This type of correction recognizes that material separated from the product capsules was returned to single- and double-shell tanks. Current ^{137}Cs capsule content is described within the IDB (DOE 1991) as 59.2 million curies decayed to December 31, 1991. Back-decaying this activity to October 1, 1982 yields an activity of 73.21 million curies. Lacking determinate data on the destination of specific fractions of these byproduct liquids, it is herein assumed that the target analyte produced during the production of 73 million Ci of ^{137}Cs has been entirely transferred into materials destined for near-surface disposal.

Open literature discussion of pertinent aspects of chemistry and chemical separations of cladding and fuel are provided by Cotton (1989), Hodgson et al. (1985), Swanson (1988), and GE (1955).

Thus, use of a summation of 140.28 million Ci value assumes that the target isotope of this calculation is entirely deposited in grout waste.

This estimate of a total content of 4.84×10^{-4} Ci of ^{226}Ra is 9 OM lower than the estimate guided by the analytical values reported. One must note, however, that the analytical values reported were "less-than" values and were reported as the detection limit for this isotope. In the above regards, the recommended base case estimate for this isotope is 3.96×10^{-6} $\mu\text{Ci/L}$, corresponding to the ORIGEN2 calculation as applied above. A calculated ^{230}Th parent concentration of 3.09×10^{-3} $\mu\text{Ci/L}$ should be included in the base case for further ingrowth of ^{226}Ra . With no further information available, no sensitivity cases are recommended.

Although caution may be advisable in the ORIGEN2 based estimate of ^{226}Ra , should ORIGEN2 errors result in actual activities several OM greater than described, it is expected that such activities will remain of little consequence in long term dose assessment.

4.4 ^{129}I Iodine Estimation

Iodine-129 is a fission product within irradiated fuel. Its presence within the waste feed is of potential concern due to its greater than 15 million year half-life and expected mobility in soil systems.

Several estimates may be made of expectations of ^{129}I concentration within grout feed wastes. The IDB (DOE 1991 [Table 2-17]) estimates site inventory to be 0.265 Ci. Calculations resulting in iodine concentrations described in Table 4 would indicate that a total of 14.8 Ci ^{129}I would be disposed. Calculation in the form of Equation 4.5, using ORIGEN2 (Hedengren 1985 [Case I, page I34]), would indicate production of 46.4 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) indicated an expectation of no more than 34 Ci to be placed in near-surface disposal.

WHC-SD-WM-TI-528, Rev. 1

Although it would obviously be beneficial to demonstrate that IDB estimates of site inventory limit ^{129}I disposition in grout wastes, the magnitude of investigation required to substantiate such is not within the scope of this document. Further, as this case is one wherein the disposal inventory would be much smaller than the next lowest estimate, the application of any of the other expressed estimates would bound such an impact analysis.

It is recommended that the base case of waste evaluation be that provided in Table 4 of $0.122 \mu\text{Ci/L}$. Two sensitivity cases based upon ORIGEN2 and the HDW-EIS are supportable with estimates of $0.381 \mu\text{Ci/L}$ and $0.279 \mu\text{Ci/L}$, respectively.

4.5 ^{126}Te Estimation

Tin-126 is a fission product within irradiated fuel. Its presence within the waste feed is of potential concern due to its 100,000 year half-life and the very short half-life (12.4 days) of its radioactive daughter ^{126}Sb .

^{126}Sn is not a typical analyte and is not described within Table 4 or the HDW-EIS. The IDB (DOE 1991 [Table 2.17]) describes a tank inventory of 104 Ci. Calculation in the manner of Equation 4.5 yields an estimate of 1,112 Ci based upon ORIGEN2 data (Hedengren 1985 [Case I, page I33]).

The recommended base case in long term dose assessment is that of waste concentrations of $9.12 \mu\text{Ci/L}$ based upon production. A sensitivity case is available as $0.853 \mu\text{Ci/L}$ based upon IDB inventory but is not highly recommended.

4.6 ^{99}Tc Estimation

Technetium-99 is primarily generated as a fission product in irradiated fuel and in activated cladding associated with irradiated fuel. In addition, it is generated from the decay of ^{99}Mo . For the purposes of this document and reality, complete molybdenum-99 decay occurs during fuel cooling. ^{99}Tc is again a concern in long term performance assessment due to its half-life of 213,000 years and potential mobility.

Table 4 estimates of ^{99}Tc disposal total to 6,311 Ci. The IDB (DOE 1991 [Table 2.17]) describes tank inventories of 13,300 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) envisioned near-surface disposal of 19,000 Ci. Production estimates based upon Equation 4.5 yield 21,581 Ci. Technetium as an activation product has been neglected from the above calculations as the fission production outweighs activation by 6 OM (Hedengren 1985 and 1986).

In view of the proximity of Table 4 estimates (based upon waste analyses) to production and pretreatment estimates, the recommended base case for waste evaluation is that described in Table 4 of $51.74 \mu\text{Ci/L}$. Sensitivity cases for evaluation would be those of production at $176.9 \mu\text{Ci/L}$ and of IDB inventory at $109 \mu\text{Ci/L}$.

WHC-SD-WM-TI-528, Rev. 1

4.7 ⁹⁴Niobium Estimation

Niobium-94 present within irradiated fuel, cladding, and resultant waste is primarily generated by neutron activation of ⁹³Nb (stable) and fission. ⁹⁴Nb retains a half-life of 20,000 years. A better estimate of waste content of this isotope is required due to its relatively long half-life, calculated concentrations (Table 4), and possible waste zone intrusion.

Table 4 DSSF Family estimates of ⁹⁴Nb are 43.3 μ Ci/L (2,634 Ci in that volume). Thorough research of ⁹⁴Nb data reported from these wastes indicates that these data are "less-than" values (see Appendix Tables 3-1 through 3-5 and 4-1 through 4-3 and their references). No information is provided in Lowe (1991) on niobium-94 concentrations, however, application of Equation 4.5 provides an ORIGEN2 fission and activation production of 0.158 Ci. This small estimate of ⁹⁴Nb may be the reason that this material is not described within either the IDB (DOE 1991) or the HDW-EIS (DOE 1987).

It is recommended that the base case of waste evaluation be that provided by production as a mean concentration of 1.30×10^{-3} μ Ci/L. This case considers analytical data (including "less-thans") and the relatively negligible production estimate described above. As no further information is available for consideration at this time, no sensitivity case is recommended in waste evaluation.

4.8 ⁷⁹Selenium Estimation

Selenium-79, with a half-life of 65,000 years, is generated by fission. A better estimate of waste content of this isotope is required due to its relative mobility and possible waste zone intrusion.

Table 4 DSSF Family estimates of ⁷⁹Se are 3.00 μ Ci/L (182 Ci in that volume). No information is provided in Lowe (1991) on selenium-79 concentrations, however, application in the form of Equation 4.5 provides an ORIGEN2 production (Hedengren 1985 [page I26]) estimate of 644 Ci. IDB (DOE 1991 [Table 2.17]) estimates of ⁷⁹Se in tanks total 65.8 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated the placement of 260 Ci of ⁷⁹Se in near-surface disposal.

The recommended base case of waste evaluation is that described by Table 4 estimates of 3.00 μ Ci/L. This base case is greater than possible sensitivity cases of 0.54 μ Ci/L and 2.13 μ Ci/L based upon the IDB and HDW-EIS, respectively, and lower than a sensitivity case of 5.28 μ Ci/L based upon production.

4.9 ¹⁴Carbon Estimation

Carbon-14 present within irradiated fuel, cladding, and resultant waste is primarily generated by neutron activation of natural carbon (¹²C and ¹³C) present in fuel and cladding as impurities. ¹⁴C retains a half-life of 5,730 years. A better estimate of waste content of this

WHC-SD-WM-TI-528, Rev. 1

isotope is required due to its expected concentrations (Table 4), and possible waste zone intrusion.

Table 4 estimates of ^{14}C including both analytical support for DSSF Family wastes and pretreatment projections yield waste expectations of $2.00\ \mu\text{Ci/L}$ (244 Ci in total volume). Applications of Equation 4.5 yield fission and activation product (Hedengren 1985 and 1986) expectations of 347 Ci of ^{14}C in the waste to be received. IDB (DOE 1991) estimates of ^{14}C in tanks total 569 Ci. The HDW-EIS (DOE 1987 [Table 5.47]) anticipated the placement of 2,300 Ci of ^{14}C in near-surface disposal.

Because of the analytical support provided for Table 4 estimates, the recommended base case for waste evaluation remains that of Table 4. Sensitivity cases available for evaluation are suggested based on production and the IDB at concentrations of $2.84\ \mu\text{Ci/L}$ and $4.66\ \mu\text{Ci/L}$, respectively.

4.10 ^{238}U Uranium Estimation

Uranium-238 is present within irradiated and non-irradiated fuel due to its abundance of approximately 99.1%. ^{238}U has a half-life of approximately 4.5×10^9 years and undergoes alpha and beta decay along the pathway $^{238}\text{U} \rightarrow ^{234}\text{Th} \rightarrow ^{234}\text{Pa} \rightarrow ^{234}\text{U} \rightarrow ^{230}\text{Th}$. Decay of ^{230}Th is described in §4.3, above. Due to the long-term impact of this decay chain of long-lived materials leading to a short-lived gaseous daughter, a better estimate of this material is sought.

Table 4 DSSF Family estimates of ^{238}U , based solely on analysis of tank 241-AN-103 and dilute evaporator feeds, result in expectations that 0.6 Ci would be disposed with these wastes. Lowe (1991) does not describe estimates of ^{238}U in feed materials to pretreatment operations. The IDB describes an estimate of 0.945 Ci (~2,800 kg) present in tank wastes. The HDW-EIS anticipated 20 Ci to be placed in near-surface disposal. Although a substantially larger amount of ^{238}U has been handled with the processing of irradiated fuel, IDB and HDW-EIS estimates are imbedded with an assumption of 99% extraction of uranium and plutonium from irradiated fuel (GE 1955). For this reason, production estimates may not be made in the manner of §4.1.2.

Although only limited analytical data supports ^{238}U estimates in the vicinity of that described by the IDB, the recommended base case for waste evaluation is that of the analytical concentrations in DSSF Family wastes ($0.010\ \mu\text{Ci/L}$). A suggested sensitivity case is that of the IDB at $7.75 \times 10^{-3}\ \mu\text{Ci/L}$. At this time no sensitivity case is suggested which would entail the OM increase anticipated in the HDW-EIS.

WHC-SD-WM-TI-528, Rev. 1

4.11 Special Estimate Summary

Table 8, below, contains a summary of recommendations for base case and sensitivity case waste evaluations developed in §§4.2 through 4.10. As supported by the individual development of these special estimates, the constituent concentrations of these recommended base and sensitivity case estimates should replace or amend those displayed in Table 4 when such is used in the evaluation of the waste or proposed disposal action. Described above, the use of IDB and HDW-EIS estimates are not recommended within this document as they have not been subjected to a comprehensive review nor have their predictions been verified against actual sample data; as such, any such use may only be considered for sensitivity cases.

WHC-SD-WM-TI-528, Rev. 1

TABLE 8: Special Estimates of Critical Isotopes			
Isotope	Recommended Base Case Waste Concentration ($\mu\text{Ci/L}$)	Recommendation Basis	Sensitivity Case Concentrations ($\mu\text{Ci/L}$) and Bases
^{241}Am	23.3	Waste Analysis/ Limited 4AN/5AN	14 Waste Analysis/Linear Regression 4AN/5AN 430 IDB 1,080 Production ²
^{238}U	0.01	Waste Analysis	0.01 IDB
^{237}Np	0.44	Waste Analysis	0.37 IDB 0.56 Production
^{230}Th	3.1 E-03	Production	None
^{226}Ra	4 E-06	Production	None
^{135}Cs	0.69	Production	0.49 IDB
^{129}I	0.12	Waste Analysis	0.38 Production 0.28 HDW-EIS
^{126}Sn	9.1	Production	0.85 IDB
^{99}Tc	51.7	Waste Analysis	180 Production 110 IDB
^{94}Nb	1.3 E-03	Production	None
^{79}Se	3.0	Waste Analysis	0.5 IDB 2.1 HDW-EIS 5.3 Production
^{14}C	2.0	Waste Analysis	2.8 Production 4.7 IDB

² Production [=] Application of ORIGEN2 data to ^{137}Cs content.

WHC-SD-WM-TI-528, Rev. 1

5.0 REFERENCES

- Browne, E., R. B. Firestone and V. S. Shirley, Table of the Radioactive Isotopes, John Wiley & Sons, New York, NY, 1986.
- Certa, P. J., 1985, "242-A Evaporator/Crystallizer FY 84 Campaign Run 84-3 Post Run Document," SD-WM-PE-018, April 30, 1985.
- Cotton, F. Albert, and G. Wilkinson, 1989, Advanced Inorganic Chemistry, Fifth Edition, John Wiley & Sons, New York, NY, 1989.
- DOE, 1987, Final Environmental Impact Statement, Disposal of Hanford Defense High-Level, Transuranic and Tank Wastes, Hanford Site, Richland, Washington, DOE/EIS-0113, U. S. Department of Energy, December 1987.
- DOE, 1988, "Record of Decision," Federal Register, 53 FR 12449, April 14, 1988.
- DOE, 1991, Integrated Data Base for 1991: U. S. Spent Fuel and Radioactive Waste Inventories, Projections, and Characteristics, DOE/RW-0006, Revision 7, October 1991, U. S. Department of Energy, Washington, D. C.
- GE, 1955, PUREX Technical Manual, HW-31000DEL, General Electric Company, Richland, WA, March 25, 1955. Publicly released August 6, 1992.
- Gratny, E. G., 1985, "242-A Evaporator/Crystallizer FY'84 Campaign 84-5 Post Run Document," SD-WM-PE-022, September 4, 1985.
- Hanlon, B. M., 1992, "Tank Farm Surveillance and Waste Status Summary Report for February 1992," WHC-EP-0182-47, May 1992.
- Hedengren, D. C., 1985, "ORIGEN2 Predictions of N Reactor Fuel Fission Product Composition," SD-CP-TI-077, Revision 0, March 14, 1985.
- Hedengren, D. C., 1986, "ORIGEN2 Predictions of N Reactor Cladding and Fuel Activation Product Composition," SD-CP-TI-094, Revision 0, November 11, 1986.
- Hedengren, D. C., and H. J. Goldberg, 1987, "ORIGEN2 Predictions of N Reactor Fuel Actinide Composition," SD-CP-TI-105, Revision 1, August 4, 1987.
- Hendrickson, D. W., 1990, "Methods and Data for Use in Determining Source Terms for the Grout Disposal Program," SD-WM-TI-355, Revision 1, March 22, 1990.
- Hendrickson, D. W., 1991a, "Radiolytic Heat Loading Calculation Methods for the Hanford Grout Disposal Facility," WHC-SD-WM-TI-455, Revision 0, January 2, 1991.

WHC-SD-WM-TI-528, Rev. 1

- Hendrickson, D. W., 1991b, "Grout Treatment Facility Waste Feed Acceptance Criteria," WHC-SD-WM-RD-019, Revision 1, October 18, 1991.
- Hendrickson, D. W. and T. L. Welsh, 1992a, "Tank 241-AP-106 Sampling and Characterization Plan," WHC-SD-WM-TP-117, Revision 0, January 30, 1992.
- Hendrickson, D. W. and T. L. Welsh, 1992b, "Tank 241-AP-105 Sampling and Characterization Plan," WHC-SD-WM-TP-130, Revision 0, April 16, 1992.
- Herting, D. L., D. B. Bechtold, B. E. Hey, B. D. Keele, L. Jensen, and T. L. Welsh, 1992, "Laboratory Characterization of Samples Taken in December 1991 (Window E) From Hanford Waste Tank 241-SY-101," WHC-SD-WM-DTR-026, Revision 0, August 20, 1992.
- Hodgson, K. M., D. L. Herting, W. W. Schultz, L. A. Bray, and J. L. Swanson, 1985, "Content and Removal of TRU Elements from Aqueous Zirconium Cladding Waste," *Proceedings of the International Symposium on Actinide/Lanthanide Separations, Honolulu, Hawaii, USA, 16-22 December 1984*, World Scientific, 1985.
- Koreski, G. M., and J. N. Strode, 1992, "Operational Waste Volume Projections," SD-WM-ER-029, Revision 16, October 28, 1992.
- Lowe, S. S., 1991, "Preliminary Material Balances for Pretreatment of NCAW, NCRW, PFP and CC Wastes," WHC-SD-WM-TI-492, Revision 0, September 10, 1991.
- O'Rourke, J. F., 1992, "Process Control Plan for 242-A Evaporator Campaign 93-1," WHC-SD-WM-PCP-008, Revision 0, November 24, 1992.
- Pontious, N. L., 1986, "242-A Evaporator/Crystallizer FY 1985 Campaign 85-3 Post-Run Document," SD-WM-PE-023, Revision 0, February 24, 1986.
- Swanson, J. L., 1988, *Recent Studies Related to Head-End Fuel Processing at the Hanford PUREX Plant*, PNL-6609, Battelle Pacific Northwest Laboratory, Richland, WA, August 1988.
- Walker, F. W., J. R. Parrington, F. Feiner, 1989, *Nuclides and Isotopes*, 14th ed., General Electric Company, San Jose, CA, 1989.
- Welsh, T. L., 1991a, "Tank 241-AN-106 Characterization Results," WHC-SD-CP-TP-065, Revision 0, March 8, 1991.
- Welsh, T. L., 1991b, "Tank 241-AW-101 Characterization Results," WHC-SD-WM-TRP-055, Revision 0, December 19, 1991.

WHC-SD-WM-TI-528, Rev. 1

APPENDIX

A-i

WHC-SD-WM-TI-528, Rev. 1

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1

GROUT TREATMENT FACILITY WASTE FEED PROJECTIONS

Waste Analyses and Calculations

<u>TABLE</u>	<u>Page</u>
1-1: Dilute Waste Summary	A-3
1-2: DSSF Family Waste Summary	A-6
1-3: DSSF Family Radiolytic Heat Loading	A-10
1-4: Pretreatment Waste Summary	A-11
2-1: 241-AP-103 Validated Analysis Data	A-14
2-2: 241-AW-106 Validated Analysis Data	A-18
2-3: 241-AW-102 Validated Analysis Data	A-22
2-3: 241-AW-102 Validated Analysis Data - cont.	A-26
2-4: 241-AP-103 Analysis Summary	A-30
2-5: 241-AW-106 Analysis Summary	A-33
2-6: 241-AW-102 Analysis Summary	A-36
2-7: Future Dilute DSSF Waste Summary	A-39
3-1: Evaporator Campaign 84-3 Analysis Data	A-43
3-2: Evaporator Campaign 84-5 Analysis Data	A-46
3-3: Evaporator Campaign 85-3 Analysis Data	A-49
3-4: Evaporator Campaign 84-5 Analysis Summary	A-52
3-5: Evaporator Campaign 85-3 Analysis Summary	A-55
4-1: Concentrated Waste Summary Data - 101AW, 103AN	A-58
4-2: Concentrated Waste Summary Data - 105AP, 106AN	A-61
4-3: Concentrated Waste Summary Data - 104AN, 105AN	A-64
5-1: Radioisotope Decay Data	A-67
<u>FIGURE</u>	<u>Page</u>
Figure A-1: Grout Feed Material Data Flowsheet.	A-1

WHC-SD-WM-TI-528, Rev. 1

THIS PAGE INTENTIONALLY LEFT BLANK

A-iv

WHC-SD-WM-TI-528, Rev. 1

Figure A-1: Grout Feed Material Data Flowsheet.

Figure A-1, comparable to Figure 2 of this document, provides the schematic of data flow used in the calculation of inventory estimates of Sections 1.0 through 4.0. Table references provided in Figure A-1 are correlated with the index to this Appendix and will allow one to follow calculations where necessary.

Radiolytic decay dates are as noted on each table.

WHC-SD-WM-TI-528, Rev. 1

THIS PAGE INTENTIONALLY LEFT BLANK

WHC-SD-WM-TI-528, Rev. 1

TABLE 1-1: Dilute Waste Summary

Dilute Waste Analyses and Estimates								
Units: Molarity: uCi/L for radionuclides; others as noted								
Component	Analytical Results			Estimate	Analytical		Overall Dilute	
	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
Ag	3.71e-07	4.46e-05	8.27e-06	3.15e-05	9.23e-06	2.36e-05	1.64e-05	2.05e-05
Al	9.12e-03	6.21e-02	1.81e-02	1.07e-01	1.95e-02	2.84e-02	4.76e-02	4.50e-02
As	6.44e-07	3.50e-05	2.01e-05	1.37e-08	1.30e-05	1.72e-05	8.85e-06	1.69e-05
B								
Ba	4.73e-07	1.26e-05	9.47e-06	6.98e-06	5.72e-06	6.28e-06	6.13e-06	5.14e-06
Be								
Bi				5.91e-05			5.91e-05	
Ca				8.48e-05			8.48e-05	
Cd	9.85e-07	2.64e-05	3.56e-06	1.10e-06	5.27e-06	1.40e-05	3.93e-06	1.23e-05
Ce								
Cr	7.10e-05	4.41e-04	2.05e-04	3.17e-04	1.73e-04	1.87e-04	2.19e-04	1.58e-04
Cu				3.89e-05			3.89e-05	
Fe	1.49e-05	1.34e-03	5.65e-04	8.12e-05	4.10e-04	6.63e-04	3.04e-04	6.09e-04
Hg	1.03e-08	5.21e-08	2.49e-08	8.22e-08	2.16e-08	2.12e-08	4.11e-08	3.17e-08
K				1.11e-01			1.11e-01	
La								
Li								
Mg	2.97e-05	4.36e-04	5.53e-04	2.20e-04	2.97e-04	2.75e-04	2.73e-04	2.32e-04
Mn	4.74e-07	1.22e-04	1.77e-05	4.87e-05	2.30e-05	6.60e-05	3.13e-05	5.39e-05
Mo				6.12e-05			6.12e-05	
Na	2.31e-01	1.73e-00	7.30e-01	1.08e-00	6.27e-01	7.63e-01	7.71e-01	6.29e-01
Nd								
Ni				1.75e-04			1.75e-04	
P				2.26e-03			2.26e-03	
Pb	1.93e-06	2.11e-04	3.86e-05	1.49e-04	4.35e-05	1.11e-04	7.75e-05	9.67e-05
Pd								
Sb								
Se	1.05e-07	1.04e-07	6.33e-08	4.30e-08	3.77e-08	2.38e-08	7.33e-08	3.08e-08
Si				4.40e-04			4.40e-04	
Sr								
Ta				1.38e-05			1.38e-05	
Ti				1.01e-05			1.01e-05	
U g/L	3.69e-03	9.47e-03	3.57e-03	2.27e-02	4.41e-03	3.34e-03	1.03e-02	8.95e-03
V								
W								
Zn	4.19e-05	1.59e-03	1.40e-04	5.04e-04	2.60e-04	8.77e-04	3.39e-04	7.17e-04
Zr				5.65e-05			5.65e-05	

WHC-SD-WM-TI-528, Rev. 1
TABLE 1-1 continued.

Dilute Waste Analyses and Estimates								
Units: Molarity: uCi/L for radionuclides; others as noted								
	Analytical Results			Estimate	Analytical		Overall Dilute	
Component	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
CN-	2.29e-05	7.63e-05	4.93e-05	1.07e-04	4.06e-05	2.67e-05	6.19e-05	3.50e-05
S-2								
NH4+	2.75e-03	3.29e-03	1.03e-02	4.97e-04	5.95e-03	4.23e-03	4.20e-03	4.25e-03
NH3								
CO3-2				2.06e-02			2.06e-02	
Cl-	1.40e-03	1.51e-02	1.31e-02	1.51e-02	7.98e-03	7.41e-03	1.03e-02	6.59e-03
F-	6.81e-03	3.43e-01	2.12e-01	4.12e-04	1.34e-01	1.69e-01	9.13e-02	1.57e-01
SO4-2	3.65e-03	3.56e-02	2.43e-02	1.15e-03	1.62e-02	1.62e-02	1.14e-02	1.56e-02
NO3-	6.51e-02	5.88e-01	2.31e-01	1.58e-01	2.00e-01	2.67e-01	1.86e-01	2.29e-01
NO2-	2.82e-02	2.08e-01	5.59e-02	1.12e-01	6.24e-02	9.69e-02	7.83e-02	7.94e-02
PO4-3	1.45e-03	7.67e-03	1.84e-03	2.28e-03	2.40e-03	3.49e-03	2.36e-03	2.93e-03
OH-	8.99e-02	5.88e-01	1.70e-01	8.78e-01	1.86e-01	2.68e-01	4.09e-01	3.69e-01
TOC g/L	1.12e-01	1.05e+00	4.91e-01	5.10e-01	3.87e-01	4.70e-01	4.27e-01	3.84e-01
TIC g/L	5.14e-01	2.36e+00	8.42e-01	1.20e+00	8.83e-01	9.85e-01	9.85e-01	8.04e-01
SPG	1.00e+00	1.09e+00	1.03e+00	1.03e+00	1.02e+00	4.27e-02	1.03e+00	3.51e-02
TotSolids								
pH								
3H	5.24e+00	1.20e+01	5.68e+00	7.10e-01	6.28e+00	3.78e+00	4.49e+00	4.64e+00
14C	4.47e-03	7.47e-02		2.70e-02	1.96e-02	4.97e-02	2.20e-02	3.59e-02
54Mn								
59Mn								
50Co	1.06e+01	6.37e+00	5.54e+00	3.30e+00	8.02e+00	2.69e+00	6.40e+00	3.16e+00
63Ni								
79Se	1.12e-02	3.98e-02		4.80e-02	1.73e-02	2.03e-02	2.72e-02	1.93e-02
90Sr	2.62e+00	2.95e+01	4.53e+01	4.20e+03	2.37e+01	2.16e+01	1.37e+03	2.09e+03
94Nb	9.31e+00	7.38e+00	5.51e+00	5.80e+00	7.49e+00	1.90e+00	7.27e+00	1.58e+00
95Nb	8.67e+00				8.67e+00		8.67e+00	
99Tc	1.08e+00	1.58e+01		1.50e+01	4.47e+00	1.11e+01	7.86e+00	8.60e+00
103Ru			2.10e+01		2.10e+01		2.10e+01	
106RuRh	2.56e+02	4.89e+02	3.98e+02	3.70e+02	3.49e+02	1.12e+02	3.56e+02	9.18e+01
113Sn	2.38e+01	5.02e+01	2.30e+01		2.89e+01	1.42e+01	2.89e+01	1.42e+01
129I	3.19e-02	4.24e-02		3.00e-02	3.41e-02	7.46e-03	3.28e-02	6.59e-03
134Cs	1.35e+01	3.97e+02	1.75e+02	1.50e+02	1.27e+02	1.94e+02	1.35e+02	1.50e+02
137Cs	6.54e+03	5.07e+04	1.52e+04	3.60e+04	1.57e+04	2.34e+04	2.22e+04	2.00e+04
144CePr	1.33e+02	2.72e+02	1.54e+02		1.59e+02	7.47e+01	1.59e+02	7.47e+01
154Eu	2.80e+01	1.51e+01	2.17e+01		2.39e+01	5.97e+00	2.39e+01	5.97e+00
155Eu	4.37e+01	6.89e+01	4.23e+01		4.63e+01	1.50e+01	4.63e+01	1.50e+01
226Ra	1.44e+02	7.76e+01	3.37e+02		2.15e+02	1.35e+02	2.15e+02	1.35e+02

WHC-SD-WM-TI-528, Rev. 1
TABLE 1-1 continued.

Dilute Waste Analyses and Estimates								
Units: Molarity: uCi/L for radionuclides; others as noted								
	Analytical Results			Estimate	Analytical		Overall Dilute	
Component	103AP	106AW	102AW	106AP	MEAN	S. Dev.	MEAN	S. Dev.
234U	6.52e-03	9.25e-03			7.11e-03	1.93e-03	7.11e-03	1.93e-03
235U	3.39e-04	9.21e-04			4.65e-04	4.11e-04	4.65e-04	4.11e-04
238U	1.26e-03	3.02e-03			1.64e-03	1.24e-03	1.64e-03	1.24e-03
237Np				3.10e-04			3.10e-04	
238Pu				1.00e-01			1.00e-01	
239/240Pu	6.97e-03	9.89e-02	3.61e-01	1.10e-01	1.65e-01	1.84e-01	1.47e-01	1.52e-01
241Am	1.14e-02	2.15e-02	2.57e-01	1.20e-01	1.14e-01	1.39e-01	1.16e-01	1.14e-01
242Cm								
243Cm								
244Cm				6.60e-03			6.60e-03	
TB			1.56e+04		1.56e+04		1.56e+04	
AT			1.86e+00		1.86e+00		1.86e+00	
Volume L	4.16e+06	1.15e+06	3.75e+06	4.29e+06	9.06e+06			

Notes: Where no values are displayed for an analyte in a tank, the mean for that analyte across the tanks is calculated as the weighted (volume) mean of those reported.
 Less-than values calculated as real values.
 Not decayed: Decay date assumed to be October 1, 1993.

WHC-SD-WM-TI-528, Rev. 1

TABLE 1-2: DSSF Family Waste Summary

DSSF Family Wastes		Decayed to				10/01/93								
Units: Holarity, uCi/L for radionuclides, others as noted														
Waste Component	Tank	Tank	Tank	Tank	Tank	Tank	Tank	[NOT Decayed]					Total Family	ConcWaste Std. Dev.
								Future DSSF	Dilutes	Required				
Ag	3.37e-05	3.09e-04	2.00e-04				1.48e-04	7.10e-05	1.64e-05	1.64e-05	8.90e-05	1.14e-04		
Al	3.44e-01	1.03e+00	1.60e-01	1.39e+00	1.74e+00	2.13e+00	1.50e-01	4.76e-02	4.76e-02	4.92e-01	7.77e-01			
As	9.61e-07	1.33e-07	8.58e-08			2.14e-03	1.00e-04	8.85e-06	2.00e-04	1.07e-03				
B														
Ba	8.08e-05	6.80e-05	4.35e-05			1.17e-04	4.40e-05	6.13e-06	4.66e-05	3.04e-05				
Be						1.78e-03			1.78e-03					
Bi	6.94e-04	5.79e-04	3.70e-04			2.30e-04		5.91e-05	3.13e-04	2.08e-04				
Ca	2.25e-03	8.26e-04	1.08e-03			2.16e-03		8.48e-05	1.00e-03	7.30e-04				
Cd	4.41e-04	1.08e-05	6.92e-06			1.42e-04	4.05e-05	3.93e-06	6.45e-05	2.04e-04				
Ce														
Cr	1.08e-02	3.09e-03	3.32e-03	1.30e-02	1.30e-02	1.63e-02	1.33e-03	2.19e-04	4.23e-03	5.49e-03				
Cu	5.90e-05	3.81e-04	2.42e-04			1.89e-04		3.89e-05	1.49e-04	1.33e-04				
Fe	1.24e-04	7.86e-04	2.00e-04	2.00e-04	2.00e-04	1.26e-03	3.15e-03	3.04e-04	1.78e-03	4.61e-04				
Hg	2.49e-07	7.82e-07	4.99e-07			7.98e-05	1.66e-07	4.11e-08	5.49e-06	3.96e-05				
K	2.76e-02	1.07e+00	8.57e-01	1.83e-01	1.57e-01	3.89e-01		1.11e-01	3.44e-01	4.21e-01				
La														
Li														
Hg	1.14e-04	2.16e-03	4.95e-04			1.18e-03	2.29e-03	2.73e-04	1.61e-03	8.96e-04				
Th	1.01e-03	4.76e-04	3.06e-04			5.24e-04	1.77e-04	3.13e-05	2.62e-04	3.04e-04				
Ho	6.94e-04	6.00e-04	3.86e-04			9.17e-04		6.12e-05	4.24e-04	2.20e-04				
Na	3.93e+00	1.00e+01	6.35e+00	1.20e+01	1.20e+01	1.46e+01	4.82e+00	7.71e-01	6.00e+00	3.98e+00				
Nd														
Ni			2.15e-03			4.09e-04		1.75e-04	6.22e-04	1.23e-03				
P	1.97e-01		1.43e-02					2.26e-03	4.98e-02	1.29e-01				
Pb	2.22e-03	1.46e-03	9.33e-04			3.47e-04	3.35e-04	7.75e-05	5.37e-04	7.96e-04				
Pd														

A-6

WHC-SD-WM-TI-528, Rev. 1
TABLE i-2 continued.

DSSF Family Wastes		Decayed to				10/01/93		[NOT Decayed]			
Units: Molarity, uCi/L for radionuclides, others as noted											
Waste Component	Tank	Tank	Tank	Tank	Tank	Tank	Future DSSF	Required Dilutes	Total Family	ConcKaste Std. Dev.	
Sb						103-AN					
Se	1.70e-06	4.20e-07	2.73e-07			103-AN	6.74e-07	7.33e-08	1.75e-04	1.32e-03	
Si		4.36e-03	3.53e-03			103-AN		4.40e-04	3.38e-03	3.34e-03	
Sn											
Ta	7 18e-07							1.88e-05	1.36e-05		
Ti	7 33e-05	9 88e-05	6 38e-05			103-AN		1.01e-05	9.14e-05	1.29e-04	
U g/L	1.68e-05	9 39e-04	6 06e-04			103-AN	3.39e-02	1.03e-02	2.11e-02	3.81e-04	
V									3.14e-04		
W									1.13e-03		
Zn	1 44e-04	4 84e-03	1 16e-03			103-AN	2.00e-03	3.39e-04	1.66e-03	2.12e-03	
Zr	3 05e-04	5 54e-04	3 59e-04					5.65e-05	2.50e-04	1.29e-04	
CN-	2 31e-04	1 03e-03	6 65e-04				3.12e-04	6.19e-05	4.01e-04	4.61e-04	
S-2											
NH4+	7 22e-03	1 45e-02	2 34e-03				5.29e-03	4.20e-03	5.75e-03	6.12e-03	
NH3				6.99e-03	2.00e-02				1.46e-02	9.20e-03	
CO3-2	3 27e-01	2 05e-01	2 53e-01	4.72e-01	3.63e-01			2.06e-02	2.12e-01	1.17e-01	
Cl-	6.94e-02	1.46e-01	7.28e-02	2.12e-01	2.40e-01		6.14e-02	1.03e-02	9.24e-02	8.60e-02	
F-	3.24e-03	4.02e-03	1.30e-01				1.03e+00	9.13e-02	6.11e-01	5.96e-02	
SO4-2	2.24e-02	1.07e-02	2.48e-02	6.82e-02	6.82e-02		1.25e-01	1.14e-02	7.63e-02	2.60e-02	
NO3-	1.10e+00	3.46e+00	2.66e+00	3.10e+00	3.12e+00		1.54e+00	1.86e-01	1.74e+00	8.32e-01	
NO2-	6.44e-01	2.19e+00	1.09e+00	1.92e+00	2.61e+00		4.80e-01	7.83e-02	9.37e-01	8.96e-01	
PO4-3	1.94e-01	2.22e-02	1.62e-02	2.94e-02	2.00e-02		1.85e-02	2.36e-03	2.69e-02	7.14e-02	
OH-	4.74e-01	5.07e+00	4.63e+00	4.09e+00	3.64e+00		1.43e+00	4.09e-01	2.15e+00	1.85e+00	
TOC g/L	3.26e+00	2.46e+00	3.92e+00	5.53e+01	4.66e+01		2.98e+00	4.27e-01	8.15e+00	2.51e+01	
TIC g/L		2.46e+00					6.79e+00	9.85e-01	5.19e+00		
SPG	1.23	1.56	1.347377	1.499809	1.503333	1.6	1.25e+00	1.03e+00	1.29e+00	1.40e-01	
TotSolids											

WHC-SD-WM-TI-528 Rev 1
TABLE i-2 continued.

USSF Family Wastes												Decayed to		10/01/93		[NOT Decayed]			
Units: Molarity, uCi/L for radionuclides; others as noted																			
Waste	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Tank	Future	Required	Total	Conc/Waste					
Component	106-AH	101-AH	105-AP	104-AH	105-AH	103-AH					DSSSF	Dilutes	Family	Std. Dev.					
pH				13.5	13.5								1.35e+01						
3H	2.68e+00	5.90e+00	7.40e+00			2.44e+00					5.58e+00	4.49e+00	5.12e+00	2.44e+00					
14C	3.35e-01	3.70e-01	2.36e-01			2.00e+00					1.51e-01	2.20e-02	2.85e-01	8.44e-01					
54Mn																			
59Mn																			
60Co	5.10e+00	1.94e+01	1.04e+01			1.20e+01					6.17e+01	6.40e+00	3.91e+01	5.92e+00					
63Ni																			
79Se	2.40e-01	4.80e-01	3.06e-01			4.30e+01					1.33e-01	2.72e-02	3.00e+00	2.13e+01					
90Sr	2.01e+03	1.01e+03	1.90e+02	9.84e+03	3.23e+03	1.05e+04					1.82e+02	1.37e+03	1.82e+03	4.55e+03					
94Nb	2.30e+01	6.82e+01	4.35e+01			7.10e+00					5.76e+01	7.27e+00	4.33e+01	2.64e+01					
95Nb											6.67e+01	8.67e+00	5.34e+01						
99Tc	6.92e+01	1.52e+02	1.79e+01			1.70e+02					3.44e+01	7.86e+00	4.87e+01	7.14e+01					
103Ru											1.62e+02	2.10e+01	1.29e+02						
106Ru/106Rh	6.78e+01	4.18e+02	9.90e+01			1.73e-01					2.68e+03	3.56e+02	1.62e+03	1.86e+02					
113Sn											2.22e+02	2.89e+01	1.78e+02						
129I	7.50e-02	3.03e-01	4.18e-02			5.20e-01					2.63e-01	3.28e-02	2.18e-01	2.23e-01					
134Cs	5.33e+00	5.20e+02	5.25e+02	6.23e+01	6.23e+01	5.75e+00					9.80e+02	1.35e+02	5.76e+02	2.54e+02					
137Cs	1.85e+05	4.83e+05	2.56e+05	7.56e+05	5.04e+05	6.13e+05					1.21e+05	2.22e+04	2.27e+05	2.15e+05					
144CePr											1.22e+03	1.59e+02	9.80e+02						
154Eu											1.84e+02	2.39e+01	1.47e+02						
155Eu											3.56e+02	4.63e+01	2.85e+02						
226Ra											1.66e+03	2.15e+02	1.32e+03						
234U						5.30e-02					5.47e-02	7.11e-03	4.45e-02						
235U						1.10e-03					3.58e-03	4.65e-04	2.71e-03						
238U						1.40e-02					1.26e-02	1.64e-03	1.04e-02						
237Np	2.11e+00	2.16e+00	1.39e+00			2.00e-02						3.10e-04	8.81e-01	9.98e-01					
238Pu	1.91e-02		3.67e-02			9.14e-01						1.00e-01	2.23e-01	5.12e-01					

A-8

Notes:

Where no values are displayed for an analyte in a tank, the mean for that analyte across the tanks is calculated as the weighted (volume) mean of those reported. Less-than values calculated as real values. NH_4^+ and NH_3 jointly summarized as NH_3 in overall summary. Concentrate waste standard deviation is calculated using the first six tank data columns.

TABLE 1-3: DSSF Family Radiolytic Heat Loading¹

137CsBa Heat Equivalents - calc by parent concentration										
	Heat Equiv (Ci) 137CsBa/Ci	106-AW	101-AW	105-AP	104-AW	105-AW	103-AW	DSSF	Dilutes	Total
60Co	3 1984	16 31067	62 17139	33 35944	0	0	38 24546	197 2573	20 48289	125 1428
90SrY	1 3967	2801 698	1403 93	265 7258	13739 06	4506 432	14726 26	254 4167	1908 786	2540 421
106RuRh	2 0004	135 5683	835 4356	197 9927	0	0	0 34575	5366 679	711 3283	3237 748
134Cs	2 1113	11 25261	1097 556	1109 116	131 4784	131 4784	12 13998	2068 492	284 2719	1215 974
137CsBa	1	185096 5	482712 2	255627 1	755513 2	504323 6	612820 1	120907 5	22239 97	227021 5
144CePr	1 6624	0	0	0	0	0	0	2035 712	264 6426	1628 363
Total		188061 3	486171 3	257233 3	769383 7	508961 5	627597 1	130830	25429 48	235769 1
Heat Load Ratio										
%Volume (feed ratio)		100.0%	75 2%	100 0%	46.6%	71.6%	57.5%	100.0%		
Rqd Dilute for blending (L)		0	1263663	0	3471668	1690847	2619377	0		

Decay Date = 10/01/93.

¹ Radiolytic heat loading is a calculation of the heat released to the waste through high energy radiolytic decay. A "¹³⁷CsBa heat equivalent" is defined as the ratio of heat provided by one curie of the referenced decay chain relative to the heat released from the decay of one curie of ¹³⁷Cs and its high energy daughter ^{137m}Ba. The basis for these calculations is provided in Hendrickson (1991a). These calculations result in evaluation of maximum feed fraction of each waste blended with dilute waste while complying with acceptance criteria for heat loading (Hendrickson, 1991b). A %Volume of 100% indicates that material may be fed without dilution.

WHC-SD-WM-TI-528, Rev. 1

TABLE 1-4: Pretreatment Waste Summary

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on 5M Na)		Mean
Ag							1.20e-03		4.08e-05
Al	4.38e-01	4.99e-01	3.00e-02	3.42e-02	4.20e-02	1.60e-02	5.50e-01	5.11e-01	4.05e-01
As							5.80e-03		1.97e-04
B					8.40e-03	9.70e-03	1.20e-02	1.69e-03	3.37e-03
Ba					2.80e-04	2.40e-04		9.75e-05	1.18e-04
Be									
Bi									
Ca					2.10e-03	3.00e-03	1.10e-01	4.77e-03	7.30e-03
Cd							4.70e-03		1.60e-04
Ce					2.10e-05	2.20e-05	4.10e-03		1.44e-04
Cr	1.05e-02	8.75e-03			7.60e-03	2.70e-03	2.70e-01	1.22e-02	1.92e-02
Cu							1.20e-02		4.08e-04
Fe	4.40e-05	1.51e-04			1.90e-03	5.80e-03	2.80e-01	1.28e-02	1.85e-02
Hg									
K	1.32e-01	1.44e-01	1.68e-01	1.25e-01	1.20e-01	8.00e-02	5.80e-02	2.04e-02	5.65e-02
La					4.70e-04	6.60e-04			1.15e-04
Li							2.30e-03		6.81e-05
Mg					1.10e-03	1.30e-03	4.90e-02	3.34e-03	4.05e-03
Mn					6.80e-05	3.00e-03	1.30e-02	5.27e-03	7.03e-03
Mo					3.20e-05	3.40e-05	5.80e-04	1.30e-03	8.54e-04
Na	5.30e-00	5.00e-00	5.30e-00	5.30e-00	5.31e-00	5.32e-00	5.30e-00	5.00e-00	5.00e-00
Nd					2.40e-04	3.40e-04	1.80e-03		1.20e-04
Ni					4.40e-04	5.30e-04	5.80e-03	2.49e-03	1.89e-03
P									
Pb							3.50e-03		1.19e-04
Pd									
Pr							1.80e-03		6.13e-05
Rb							1.80e-02		5.13e-04
Si					3.70e-02	3.70e-02	2.90e-02		9.77e-03
Sn									
Ta									
Tb					1.90e-04	1.70e-04	1.80e-03		9.95e-05
Ti					1.40e-00	2.19e-00	1.74e-00	1.59e-03	4.24e-01
V									
W									
Zn					9.70e-05	3.80e-05	4.10e-03	3.97e-04	4.08e-04

WHC-SD-WM-TI-528, Rev. 1
TABLE 1-4 continued.

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on SM Na)		Mean
Zr	2.90e-05	1.28e-05			2.40e-01	2.40e-01	2.30e-03	4.97e-04	5.09e-02
CN-									
S-2									
NH4+									
NH3					1.40e-02	2.60e-02			3.99e-03
CO3-2							3.30e-01		1.12e-02
Cl-					6.60e-03	3.70e-03	1.10e-01	7.88e-02	5.51e-02
F-					1.69e+00	1.67e+00	2.20e-01	5.22e-02	3.95e-01
SO4-2	1.43e-01	2.19e-01			5.00e-04	3.70e-03	7.20e-02	5.91e-02	6.70e-02
NO3-	1.66e+00	1.80e+00	3.78e+00	4.09e+00	7.40e-01	7.70e-01	3.50e+00	5.13e+00	3.76e+00
NO2-	4.10e-01	4.48e-01	1.20e-02	1.31e-02	3.60e-02	2.20e-02	5.50e-01		7.42e-02
PO4-3	2.37e-02	3.21e-03					4.40e-01	2.93e-02	3.46e-02
OH-	1.29e+00		8.80e-01		2.60e-01	2.90e-01	6.50e-01		1.55e-01
TOC g/L	6.20e-02								3.54e-03
TIC g/L									
TPG					1.48	1.47	1.43		
Total Solids									
DH									
3H									
14C	1.70e+01	4.48e+01			5.90e-01	6.50e-01	1.50e+00		3.71e+00
54Mn									
59Mn									
60Co					5.00e+01	6.10e+01	1.20e+02		1.56e+01
53Ni							3.50e+03		1.19e+02
79Se									
90Sr	1.53e+03	2.91e+03			2.20e+03	2.40e+03	5.80e+04	3.32e+04	2.39e+04
94Nb									
95Nb					2.40e+04	6.00e+03			3.49e+03
99Tc	2.34e+02	5.92e+02			4.30e+00	4.70e+00	2.10e+02		5.47e+01
103Ru									
106RuRh	1.26e-03	5.35e+03			9.40e-03	5.60e+03	1.20e+03		2.07e+03
113Sn									
129I	6.38e-02	1.78e-01			1.10e-02	1.20e-02	2.90e-01		2.51e-02
134Cs					3.30e-02	2.60e-02	7.30e+01		5.21e+01
137Cs	4.75e+04	1.36e+05	1.71e+06	4.89e+06	1.50e+04	1.10e+04	1.50e+05	9.72e+03	3.67e+04
141CePr					1.20e+04	6.90e+03	1.20e+03		2.12e+03
154Eu					9.30e+00	6.80e+01	1.20e+03		4.79e+01

WHC-SD-WM-TI-528, Rev. 1
TABLE 1-4 continued.

Preliminary Pretreatment Material Balances (WHC-SD-WM-TI-492)									
Units: Molarity: uCi/L for radionuclides; others as noted									
Waste	NCAW Str. 12		NCAW Str. 13		Stream 27		PFP Waste	CC Waste	Total
Component	AZ 101	AZ 102	AZ 101	AZ 102	103-AW	105-AW	(Based on SM Na)		Mean
155Eu					1.10e+01	8.00e+01	1.20e+03		4.91e+01
226Ra									
234U									
235U									
238U									
237Np							8.51e-03		2.90e-04
238Pu	2.71e-01	8.30e-01			9.15e-02	2.29e-01			9.41e-02
239/240Pu	1.87e+00	3.03e+00			1.18e+00	1.97e+00	4.90e+01	1.28e+00	3.08e+00
241Am	3.33e+01	3.14e+02			9.79e-02	8.48e-01	1.73e+02	3.00e+00	2.78e+01
242Cm									
243Cm									
244Cm							4.86e-01		1.65e-02
TB									
AT									
Volume L	3.49e+06	3.50e+06	1.12e+05	1.12e+05	7.57e+06	5.30e+06	2.08e+06	3.90e+07	6.12e+07
Additional analytes described for these wastes									
95Zr					1.20e+04	2.80e+03			1.73e+03
125Sb					2.50e+03	2.20e+03	1.20e+03		5.41e+02
152Eu							1.20e+02		4.08e+00
241Pu	1.69e-01	4.51e-01			1.47e-01	4.08e-01			9.90e+00
243Pu					2.28e-05	1.49e-04			1.57e-05

Note: Not Decayed. Decay date assumed as October 1, 1993.

WHC-SD-WM-TI-528, Rev. -

TABLE 2-1: 241-AP-103 Validated Analysis Data

Tank 103AP Analyses		Sample	933	934	935	936	937	941	942	943	944	945	949
Component	Units												
Ag	ppm	107 868	<	0 04	0 04	0 04	0 04	0 04	0 04	0 04	0 04	0 04	949
Al	ppm	26 98154	<	102	76	307	230	259	560	104	171	550	Comp
As	ppm	74 9216		0 052	0 035	0 055	0 045	0 039	0 084	0 028	0 035	0 061	
B	ppm	10 81											
Ba	ppm	137 33	<	0 065	0 065	0 065	0 065	0 065	0 065	0 065	0 065	0 065	
Be	ppm	9 01218											
Bi	ppm	208 9804											
Ca	ppm	40 08											
Cd	ppm	112 41		0 0715	0 048	0 133	0 0645	0 124	0 183	0 081	0 097	0 18	
Ce	ppm	140 12											
Cr	ppm	51 996		3 535	2 05	4 87	3 38	4 48	6 6	0 353	0 415	6 4	
Cu	ppm	63 546											
Fe	ppm	55 847	<	0 435	0 481	0 99	0 435	1 355	2 67	0 63	0 435	0 435	
Hg	ppm	200 59	<	0 0017	0 0017	0 0017	0 0017	0 002		0 005	0 002	0 002	
K	ppm	39 0983											
La	ppm	138 9055											
Li	ppm	6 941											
Mg	ppm	24 305	<	1 085	1 03	1 53	1 15	1 14	0 255	0 255	0 255	0 255	
Mn	ppm	54 938	<	0 015	0 015	0 0515	0 015	0 062	0 034	0 015	0 015	0 023	
Mo	ppm	95 94											
Na	ppm	22 98977		3665	2320	2460	3820	2050	11700	3700	4870	12000	
Nd	ppm	141 24											
Ni	ppm	58 7											
P	ppm	10 97376											
Pb	ppm	207 2	<	0 4	0 4	0 4	0 4	0 4	0 4	0 4	0 4	0 4	
Pd	ppm	106 4											
Sb	ppm	121 75											

[illegible]

R.97

WHC-SD-WM-TI-528 Rev. 1
TABLE 2-1 continued.

Tank 103AP Analyses			Sample	933	934	935	936	937	941	942	943	944	945	949
17 Dec 91														
Component	Units	W												Comp
243(m)	uCi/l													
244(m)	uCi/l													
IB	uCi/l													
AI	uCi/l													

TABLE 2-2: 241-AW-106 Validated Analysis Data

Rank 106AW Analyses		Sample																		
20-Sep-91	Component	Units	HW	<	318	319	320	321	322	326	327	328	329	330	348					
Ag		ppm	107 868	<R	2 28	7 44	4 8	4 8	4 8	4 8	4 8	4 8	4 8	4 8	4 8					
Al		ppm	26 98154	R	1450	1060	1350	1380	972	1395	4970	1400	1380	1400	1400					
As		ppm	74 9216		2 455	2 33	2 37	2 59	2 62	2 48	4 14	2 49	2 35	2 41						
B		ppm	10 81																	
Ba		ppm	137 33	<R	1 07	1 8	1 8	1 8	1 8	1 8	1 8	1 8	1 8	1 8	1 8					
Be		ppm	9 01218																	
Bi		ppm	208 9804																	
Ca		ppm	40 08																	
Cd		ppm	112 41	<R	1 57	2 4	2 4	2 4	2 4	3 29	4 2	4 38	3 36	3 33						
Ce		ppm	140 12																	
Cr		ppm	51 996	R	24 3	20 8	14 8	22 9	15 3	24 95	36 7	21 2	25 4	22 8						
Cu		ppm	63 546																	
Fe		ppm	55 847	<R	126	52 2	52 2	52 2	52 2	52 2	52 2	52 2	202	52 2						
Hg		ppm	200 59	<R	0 0446	0 005	0 005	0 005	0 005	0 005	0 005	0 005	0 02	0 005						
K		ppm	39 0983																	
La		ppm	138 9055																	
Li		ppm	6 941																	
Mg		ppm	24 305	<R	1 1	6 6	6 6	6 6	6 6	16 3	24 9	6 6	10 8	9 78						
Mn		ppm	54 938	R	24 6	5 58	5 22	4 08	5 46	3 245	7 62	3 36	4 56	3 51						
Mo		ppm	95 94																	
Na		ppm	22 98977	R	37900	26400	36200	36000	26600	38100	85200	37100	37100	37100						
Nd		ppm	144 24																	
Ni		ppm	58 7																	
P		ppm	30 9/3/6																	
Pb		ppm	207 2	<R	11	48 6	48	40 8	48	48	48	48	48	48						
Pd		ppm	106 4																	
Sb		ppm	121 75																	

WHC-SD-WM-TI-528, Rev 1
TABLE 2-2 continued.

Tank 106AM Analyses		Sample	318	319	320	321	322	326	327	328	329	330	348
Component	Units												
Se	ppm	HW	78 96	0 01	0 001	0 01	0 001	0 01	0 01	0 01	0 01	0 01	Comp
Si	ppm	28 0855											
Sn	ppm	118 69											
Ta	ppm	180 9479											
Ti	ppm	47 9											
U	g/L	238 029											
V	ppm	50 9415											0.00947
W	ppm	183 85											
Zn	ppm	65 48	R	138	121	78	128	77.5	194	41.4	105	73.2	
Zr	ppm	91 22											
(H)	ppm	26 0111		2 49	2 43	2 49	2 57	0 836	0 761	2 4	0 37	2 1	
S-2	ppm	J2 06											
NH4+	H	18 0383	<	0 0033	0 00149	0 0015	0 00139	0 002	0 018	0 001	0 002	0 001	
NH3	H	17 0304											
CO3-2	H	60 0092											
Cl-	ppm	35 453		431	447	470	489	432.5	1180	455	450	441	
F-	ppm	18 9984		5900	6680	5840	5830						
SO4-2	ppm	96 0576		2480	2560	2580	2490	2335	10600	2550	2350	2350	
NO3-	ppm	62 0049		31600	36800	31400	32500	31100	75900	31900	30100	29800	
NO2-	ppm	46 0055		8140	7350	7470	7450	8060	24000	8270	8060	7900	
PO4-3	ppm	94 97136		589	586	611	595	587.5	1820	605	584	653	
OH-	H	17 0073		0 518	0 511	0 53	0 588	0 467	1 3	0 556	0 531	0 318	
TOC	g/L	12 011		0 886	0 88	0 776	0 918	0 873	2 39	0 952	0 946	0 875	
TIC	g/L	12 011		2 47	2 27	2 16	2 3	1 995	3 97	2 17	2 15	2 03	
SP6	g/mL			1 0077	1 0757	1 079	1 0795	1 084	1 188	1 079	1 075	1 102	
totSolids	wt%												
pH													
311	uCi/L												12

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-2 continued.

Rank 106AII Analyses		MW		Sample	318	319	320	321	322	326	327	328	329	330	348
20-Sep-91	Component														
	Units														Comp
14C	uCi/L														0.0747
54Mn	uCi/L														
59Mn	uCi/L														
60Co	uCi/L														6.37
63Ni	uCi/L														
79Se	uCi/L														0.0398
90Sr	uCi/L														29.45
94Nb	uCi/L														7.38
95Nb	uCi/L														
99Tc	uCi/L														16.8
103Ru	uCi/L														
106RuRh	uCi/L														489
113Sn	uCi/L														50.15
129I	uCi/L														0.0424
134Cs	uCi/L														397
137Cs	uCi/L														50650
144CePr	uCi/L														271.5
154Eu	uCi/L														16.05
155Eu	uCi/L														68.85
226Ra	uCi/L														77.55
234U	uCi/L														0.00925
235U	uCi/L														0.00092
238U	uCi/L														0.00302
237Np	uCi/L														
238Pu	uCi/L														
239/240Pu	uCi/L														0.09885
241Am	uCi/L														0.02145
242Cm	uCi/L														

[illegible]

TABLE 2-3: 241-AW-102 Validated Analysis Data

Tank 102AW Analyses													
14 Jun 91													
Component	Units	FW		Sample									
Ag	ppm	107.868	<	9394									
Al	ppm	26.98154	<	1.15	0.82	0.8	0.8						
As	ppm	74.9216		476	482	491	501						
B	ppm	10.81											
Ba	ppm	137.33	<	1.3	1.3	1.3	1.3						
Be	ppm	9.01218											
Bi	ppm	208.9804											
Ca	ppm	40.08											
Cd	ppm	112.41	<	0.4	0.4	0.4	0.4						
Ce	ppm	140.12											
Cr	ppm	51.996		10.75	10.4	10.9	10.6						
Cu	ppm	63.546											
Fe	ppm	55.847		45.65	50.6	23.9	6.17						
Hg	ppm	200.59	<										
K	ppm	39.0983											
La	ppm	138.9055											
Li	ppm	6.941											
Mg	ppm	24.305		9.55	13.7	13.3	17.2						
Mn	ppm	54.938	<	0.3	0.3	3	0.3						
Pb	ppm	95.94											
Ra	ppm	22.98977		16550	16600	17000	17000						
Rd	ppm	144.24											
Rh	ppm	58.7											
P	ppm	30.97376											
Pb	ppm	207.2	<	8	8	8	8						
Pd	ppm	106.4											
Sb	ppm	121.75											

WHC-SD-WM-TI-528 Rev. 1
TABLE 2-3 continued.

Tank 102AP Analysis			Sample	9395	9396	9397	9401	9402	9403	9404
Component	Units	HI	9394							
Se	ppm	78.96	<				0.005	0.005	0.005	0.005
Si	ppm	28.0855								
Sn	ppm	118.69								
Ta	ppm	180.9479								
Ti	ppm	47.9								
U	g/l	238.029								
V	ppm	50.9415								
W	ppm	183.85								
Zn	ppm	65.38	3.245	7.3	5.1	20.9				
Zr	ppm	91.22								
CN	ppm	26.0177								
S-2	ppm	32.06								
NH4+	M	18.0383	<							
NH3	M	17.0304								
CO3-2	M	60.0092								
Cl-	ppm	35.453								
F-	ppm	18.9984								
SO4-2	ppm	96.0576								
NO3-	ppm	62.0049								
NO2-	ppm	46.0055								
PM4-3	ppm	94.97136								
NI	M	17.0073								
TOC	g/L	12.011								
TIC	g/L	12.011								
SPG	g/mL									
TotSolids	wt%									
pH										
3H	uCi/L									

WHC-SD-WM-TI-528 Rev. 1
TABLE 2-3 continued.

[illegible]

[illegible]

WHC-SD-WM-TI-528, Rev. 1

TABLE 2-3: 241-AW-102 Validated Analysis Data - cont.

Tank 102AW Analyses		Sample	<	MU	9408	9409	9410	9411	9415	9416	9417	9418
Component	Units											
Ag	ppm		<	107 868								
Al	ppm			26 98154								
As	ppm			74 9216								
B	ppm			10 81								
Ba	ppm		<	137 33								
Be	ppm			9 01218								
Bi	ppm			208 9804								
Ca	ppm			40 08								
Cd	ppm		<	112 41								
Ce	ppm			140 12								
Cr	ppm			51 996								
Cu	ppm			63 546								
Fe	ppm			55 847								
Hg	ppm		<	200 59								
K	ppm			39 0983								
La	ppm			138 9055								
Li	ppm			6 941								
Mg	ppm			24 305								
Mn	ppm		<	54 938								
Mo	ppm			95 94								
Ni	ppm			22 98977								
Nd	ppm			144 24								
NI	ppm			58 7								
P	ppm			30 97376								
Pb	ppm		<	207 2								
Pd	ppm			106 4								
Sb	ppm			121 75								

Tank 102AW Analyses		Units	MW	Sample	9408	9409	9410	9411	9415	9416	9417	9418
14-Jun-91	Component											
Se		ppm	78.96									
Si		ppm	28.0855									
Sn		ppm	118.69									
Ta		ppm	180.9479									
Ti		ppm	47.9									
U		g/L	238.029						0.0045	0.0019	0.004	0.004
V		ppm	50.9415									
W		ppm	183.85									
Zn		ppm	65.38									
Zr		ppm	91.22									
CH-		ppm	26.0177	1.22	1.32	1.21	1.38					
S-2		ppm	32.06									
HM4+		H	18.0383	0.008	0.008	0.00347	0.023					
HM3		H	17.0304									
CO3-2		H	60.0092									
Cl-		ppm	35.453	623	175	582	481					
F-		ppm	18.9984	4280	3870	4090	3900					
SO4-2		ppm	96.0576	2190	2620	2550	1980					
NO3-		ppm	62.0049	14250	14400	14100	14600					
NO2-		ppm	46.0055	2520	2640	2540	2580					
PO4-3		ppm	94.97136	178	179	174	167					
OH-		H	17.0073	0.177	0.154	0.179						
TOC		g/L	12.011	0.407	0.616	0.517	0.424					
TIC		g/L	12.011	0.684	0.856	1.07	0.758					
SPG		g/mL		1.024	1.024	1.027	1.026					
TotSolids		wt%										
pH												
3H		g/L							5.88	5.65	5.56	5.64

[illegible]

WHC-SD-WM-TI-528, Rev. 1

TABLE 2-4: 241-AP-103 Analysis Summary

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	10	<	0.04	4.74e-10	3.71e-07	4.40e-15
Al	ppm	10		246.2	179.8245	9.12e-03	6.66e-03
As	ppm	10		0.04825	0.016199	6.44e-07	2.16e-07
B	ppm						
Ba	ppm	10	<	0.065	0	4.73e-07	0.00
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	10		0.11075	0.046661	9.85e-07	4.15e-07
Ce	ppm						
Cr	ppm	10		3.6943	2.207772	7.10e-05	4.25e-05
Cu	ppm						
Fe	ppm	10	<	0.8301	0.717151	1.49e-05	1.28e-05
Hg	ppm	9	<	0.002067	0.0011	1.03e-08	5.48e-09
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	10	<	0.721	0.508575	2.97e-05	2.09e-05
Mn	ppm	10	<	0.02604	0.017424	4.74e-07	3.17e-07
Mo	ppm						
Na	ppm	10		5312.5	3689.37	2.31e-01	1.60e-01
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	10	<	0.4	0	1.93e-06	0.00
Pd	ppm						
Sb	ppm						
Se	ppm	10	<	0.0083	0.006203	1.05e-07	7.86e-08
Si	ppm						

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	1		0.00369			
V	ppm						
W	ppm						
Zn	ppm	10	<	0.27405	0.374165	4.19e-06	5.72e-06
Zr	ppm						
CN-	ppm	10	<	0.5963	0.150586	2.29e-05	5.79e-06
S-2	ppm						
NH4+	M	10	<	2.75e-03	1.74e-03	2.75e-03	1.74e-03
NH3	M						
CO3-2	M						
Cl-	ppm	10		49.475	27.30044	1.40e-03	7.70e-04
F-	ppm	10		129.325	89.98548	6.81e-03	4.74e-03
SO4-2	ppm	10		350.2	131.9398	3.65e-03	1.37e-03
NO3-	ppm	10		4039	3081.787	6.51e-02	4.97e-02
NO2-	ppm	10		1299.3	264.141	2.82e-02	5.74e-03
PO4-3	ppm	10		138.1	16.27165	1.45e-03	1.71e-04
OH-	M	10		0.089866	0.066742	8.99e-02	6.67e-02
TOC	g/L	10		0.11203	0.024337		
TIC	g/L	10		0.51385	0.062412		
SPG	g/mL	10		1.00366	0.009484		
TotSolids	wt%						
pH							
3H	uCi/L	1		5.24			
14C	uCi/L	1		0.00447			
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	4	<	10.615	1.122304		

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-4 continued.

Tank 241-AP-103 Analyses							
17-Dec-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L	1		0.01115			
90Sr	uCi/L	1		2.62			
94Nb	uCi/L	1		9.31			
95Nb	uCi/L	2	<	8.6725	0.887419		
99Tc	uCi/L	1		1.08			
103Ru	uCi/L						
106RuRh	uCi/L	2	<	266	104.6518		
113Sn	uCi/L	2	<	23.8	8.768124		
129I	uCi/L	1	<	0.03185			
134Cs	uCi/L	11	<	10.45455	2.732217		
137Cs	uCi/L	11		6544.091	1042.609		
144CePr	uCi/L	2	<	132.825	52.57339		
154Eu	uCi/L	4	<	27.9875	4.905843		
155Eu	uCi/L	10	<	43.695	18.37012		
226Ra	uCi/L	2	<	143.5	142.1285		
234U	uCi/L	1		0.00652			
235U	uCi/L	1		0.000339			
238U	uCi/L	1		0.001257			
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	1	<	0.00697			
241Am	uCi/L	1	<	0.01135			
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						

WHC-SD-WM-TI-528, Rev. 1

TABLE 2-5: 241-AW-106 Analysis Summary

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	10	<R	4.812	1.216487	4.46e-05	1.13e-05
Al	ppm	10	R	1675.7	1168.542	6.21e-02	4.33e-02
As	ppm	10		2.6235	0.541449	3.50e-05	7.23e-06
B	ppm						
Ba	ppm	10	<R	1.727	0.230846	1.26e-05	1.68e-06
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	10	<R	2.973	0.89098	2.64e-05	7.93e-06
Ce	ppm						
Cr	ppm	10	R	22.915	6.087604	4.41e-04	1.17e-04
Cu	ppm						
Fe	ppm	10	<R	74.56	50.42793	1.34e-03	9.03e-04
Hg	ppm	10	<R	0.01046	0.012889	5.21e-08	6.43e-08
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	10	<R	10.588	9.392319	4.36e-04	3.86e-04
Mn	ppm	10	R	6.7235	6.419986	1.22e-04	1.17e-04
Mo	ppm						
Na	ppm	10	R	39770	16568.78	1.73e+00	7.21e-01
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	10	<R	43.64	11.6957	2.11e-04	5.64e-05
Pd	ppm						
Sb	ppm						
Se	ppm	10	<	0.0082	0.003795	1.04e-07	4.81e-08
Si	ppm						

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-5 continued.

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	1		0.00947			
V	ppm						
W	ppm						
Zn	ppm	10	R	103.77	43.29342	1.59e-03	6.62e-04
Zr	ppm						
CN-	ppm	10		1.98515	0.982056	7.63e-05	3.77e-05
S-2	ppm						
NH4+	M	10	<	3.29e-03	5.10e-03	3.29e-03	5.10e-03
NH3	M						
CO3-2	M						
Cl-	ppm	10		535.3	229.5887	1.51e-02	6.48e-03
F-	ppm	5		6512	1066.804	3.43e-01	5.62e-02
SO4-2	ppm	10		3418	2564.419	3.56e-02	2.67e-02
NO3-	ppm	10		36454.99	13999.66	5.88e-01	2.26e-01
NO2-	ppm	10		9575	5092.607	2.08e-01	1.11e-01
PO4-3	ppm	10		728.862	384.3368	7.67e-03	4.05e-03
OH-	M	10		0.58838	0.261077	5.88e-01	2.61e-01
TOC	g/L	10		1.0466	0.475226		
TIC	g/L	10		2.3595	0.582773		
SPG	g/mL	10		1.08595	0.04359		
TotSolids	wt%						
pH							
3H	uCi/L	1		12			
14C	uCi/L	1		0.0747			
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	1	<	6.37			

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-5 continued.

Tank 241-AW-106 Analyses							
20-Sep-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L	1		0.0398			
90Sr	uCi/L	1		29.45			
94Nb	uCi/L	1	<	7.38			
95Nb	uCi/L						
99Tc	uCi/L	1		16.8			
103Ru	uCi/L						
106RuRh	uCi/L	1	<	489			
113Sn	uCi/L	1	<	50.15			
129I	uCi/L	1	<R	0.0424			
134Cs	uCi/L	1	<	397			
137Cs	uCi/L	1		50650			
144CePr	uCi/L	1	<	271.5			
154Eu	uCi/L	1	<	16.05			
155Eu	uCi/L	1	<	68.85			
226Ra	uCi/L	1	<	77.55			
234U	uCi/L	1		0.009252			
235U	uCi/L	1		0.000921			
238U	uCi/L	1		0.003015			
237Nd	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	1	<	0.09885			
241Am	uCi/L	1	<	0.02145			
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						

TABLE 2-6: 241-AW-102 Analysis Summary

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Ag	ppm	4	<	0.8925	0.171925	8.27e-06	1.59e-06
Al	ppm	4		487.5	10.90871	1.81e-02	4.04e-04
As	ppm	4		1.50625	0.094989	2.01e-05	1.27e-06
B	ppm						
Ba	ppm	4	<	1.3	8.43e-09	9.47e-06	6.14e-14
Be	ppm						
Bi	ppm						
Ca	ppm						
Cd	ppm	4	<	0.4	4.21e-09	3.56e-06	3.75e-14
Ce	ppm						
Cr	ppm	4		10.6625	0.2136	2.05e-04	4.11e-06
Cu	ppm						
Fe	ppm	4		31.58	20.52946	5.65e-04	3.68e-04
Hg	ppm	4	<	0.005	1.45e-11	2.49e-08	7.22e-17
K	ppm						
La	ppm						
Li	ppm						
Mg	ppm	4		13.4375	3.128198	5.53e-04	1.29e-04
Mn	ppm	4	<	0.975	1.35	1.77e-05	2.46e-05
Mo	ppm						
Na	ppm	4		16787.5	246.2214	7.30e-01	1.07e-02
Nd	ppm						
Ni	ppm						
P	ppm						
Pb	ppm	4	<	8	0	3.86e-05	0.00
Pd	ppm						
Sb	ppm						
Se	ppm	4	<	0.005	1.45e-11	6.33e-08	1.83e-16
Si	ppm						

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-6 continued.

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
Sn	ppm						
Ta	ppm						
Ti	ppm						
U	g/L	4		3.67e-03	1.23e-03	1.54e-08	5.15e-09
V	ppm						
W	ppm						
Zn	ppm	4		9.13625	8.01573	1.40e-04	1.23e-04
Zr	ppm						
CN-	ppm	4		1.2825	0.081803	4.93e-05	3.14e-06
S-2	ppm						
NH4+	M	4	<	0.01033	0.008471	1.03e-02	8.47e-03
NH3	M						
CO3-2	M						
Cl-	ppm	4		465.25	202.4918	1.31e-02	5.71e-03
F-	ppm	4		4035	190.1754	2.12e-01	1.00e-02
SO4-2	ppm	4		2335	302.4897	2.43e-02	3.15e-03
NO3-	ppm	4		14337.5	213.6001	2.31e-01	3.44e-03
NO2-	ppm	4		2570	52.91503	5.59e-02	1.15e-03
PO4-3	ppm	4		174.5	5.446712	1.84e-03	5.74e-05
OH-	M	3		0.17	0.013892	1.70e-01	1.39e-02
TOC	g/L	4		0.491075	0.096256		
TIC	g/L	4		0.842	0.167531		
SPG	g/mL	4		0.025275	0.001578		
TotSolids	wt%						
pH							
3H	uCi/L	4		5.6825	0.137689		
14C	uCi/L						
54Mn	uCi/L						
59Mn	uCi/L						
60Co	uCi/L	4	<	5.635	2.382737		

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-6 continued.

Tank 241-AW-102 Analyses							
14-Jun-91						Molarity	
Component	Units	n	<	Mean	S.Dev.	Mean	S.Dev.
63Ni	uCi/L						
79Se	uCi/L						
90Sr	uCi/L	4	R	45.3175	71.79467		
94Nb	uCi/L	4	<	5.5075	1.903827		
95Nb	uCi/L						
99Tc	uCi/L						
103Ru	uCi/L	4	<	21.025	7.30542		
106RuRh	uCi/L	4	<	397.875	88.20466		
113Sn	uCi/L	4	<	28	9.40709		
129I	uCi/L						
134Cs	uCi/L	4	<	174.875	11.06327		
137Cs	uCi/L	4		15237.5	593.5416		
144CePr	uCi/L	4	<	154.175	62.61301		
154Eu	uCi/L	4	<	21.7	11.53798		
155Eu	uCi/L	4	<	42.2625	20.86725		
226Ra	uCi/L	4	<	337.125	50.0506		
234U	uCi/L						
235U	uCi/L						
238U	uCi/L						
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L	4		0.361225	0.619461		
241Am	uCi/L	4		0.25745	0.373926		
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L	4		15625	3118.092		
AT	uCi/L	4	<R	1.86	0.36		

TABLE 2-7: Future Dilute DSSF Waste Summary²

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW.3AP	Composite	Evap.
Component	MEAN	product
Ag	9.23e-06	7.10e-05
Al	1.95e-02	1.50e-01
As	1.30e-05	1.00e-04
B		
Ba	5.72e-06	4.40e-05
Be		
Bi		
Ca		
Cd	5.27e-06	4.05e-05
Ce		
Cr	1.73e-04	1.33e-03
Cu		
Fe	4.10e-04	3.15e-03
Hg	2.16e-08	1.66e-07
K		
La		
Li		
Mg	2.97e-04	2.29e-03
Mn	2.30e-05	1.77e-04
Mo		
Na	6.27e-01	4.82e+00
Nd		
Ni		
P		

²

241-AP-106 concentration estimates developed in WHC-SD-WM-TP-117.

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-7 continued.

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
Pb	4.35e-05	3.35e-04
Pd		
Sb		
Se	8.77e-08	6.74e-07
Si		
Sn		
Ta		
Ti		
U g/L	4.41e-03	3.39e-02
V		
W		
Zn	2.60e-04	2.00e-03
Zr		
CN-	4.06e-05	3.12e-04
S-2		
NH4+	5.95e-03	5.29e-03
NH3		
CO3-2		
Cl-	7.98e-03	6.14e-02
F-	1.34e-01	1.03e+00
SO4-2	1.62e-02	1.25e-01
NO3-	2.00e-01	1.54e+00
NO2-	6.24e-02	4.80e-01
PO4-3	2.40e-03	1.85e-02
OH-	1.86e-01	1.43e+00
TOC g/L	3.87e-01	2.98e+00
TIC g/L	8.83e-01	6.79e+00

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-7 continued.

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW.3AP	Composite	Evap.
Component	MEAN	product
SPG	1.02e+00	~1.25
TotSolids		
pH		
3H	6.28e+00	5.58e+00
14C	1.96e-02	1.51e-01
54Mn		
59Mn		
60Co	8.02e+00	6.17e+01
63Ni		
79Se	1.73e-02	1.33e-01
90Sr	2.37e+01	1.82e+02
94Nb	7.49e+00	5.76e+01
95Nb	8.67e+00	6.67e+01
99Tc	4.47e+00	3.44e+01
103Ru	2.10e+01	1.62e+02
106RuRh	3.49e+02	2.68e+03
113Sn	2.89e+01	2.22e+02
129I	3.41e-02	2.63e-01
134Cs	1.27e+02	9.80e+02
137Cs	1.57e+04	1.21e+05
144CePr	1.59e+02	1.22e+03
154Eu	2.39e+01	1.84e+02
155Eu	4.63e+01	3.56e+02
226Ra	2.15e+02	1.66e+03
234U	7.11e-03	5.47e-02
235U	4.65e-04	3.58e-03
238U	1.64e-03	1.26e-02

WHC-SD-WM-TI-528, Rev. 1
TABLE 2-7 continued.

Dilute Waste Analyses and Estimates		
Units: Molarity; uCi/L for radionuclides; others as noted		
2&6AW,3AP	Composite	Evap.
Component	MEAN	product
²³⁷ Np		
²³⁸ Pu		
^{239/240} Pu	1.65e-01	1.27e+00
²⁴¹ Am	1.14e-01	8.80e-01
²⁴² Cm		
²⁴³ Cm		
²⁴⁴ Cm		
TB		
AT		
Volume L	9.06e+06	1177332
WVR		87.00%

Note: Evaporator product calculated as 87% WVR.

WHC-SD-WM-TI-528, Rev. 1

TABLE 3-1: Evaporator Campaign 84-3 Analysis Data³

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
Ag	ppm	107.868			
Al	M	26.9815		1.81	
As	ppm	74.9216			
B	ppm	10.81			
Ba	ppm	137.33			
Be	ppm	9.01218			
Bi	ppm	208.98			
Ca	ppm	40.08			
Cd	ppm	112.41			
Ce	ppm	140.12			
Cr	ppm	51.996		0.013	
Cu	ppm	63.546			
Fe	ppm	55.847		2e-04	
Hg	ppm	200.59			
K	ppm	39.0983			
La	ppm	138.906			
Li	ppm	6.941			
Mg	ppm	24.305			
Mn	ppm	54.938			
Mo	ppm	95.94			
Na	M	22.9898			
Nd	ppm	144.24			
Ni	ppm	58.7			
P	ppm	30.9738			
Pb	ppm	207.2			
Pd	ppm	106.4			
Sb	ppm	121.75			
Se	ppm	78.96			
Si	ppm	28.0855			
Sn	ppm	118.71			
Ta	ppm	180.948			
Ti	ppm	47.88			
U	g/L	238.029			
V	ppm	50.9415			
W	ppm	183.85			
Zn	ppm	65.38			

³

Reference: SD-WM-PE-018.

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-1 continued.

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
Zr	ppm	91.22			
CN-	ppm	26.0177			
S-2	ppm	32.06			
NH4+	M	18.0383			
NH3	M	17.0304			
CO3-2	M	60.0092		0.28	
Cl-	M	35.453			
F-	M	18.9984			
SO4-2	M	96.0576		0.016	
NO3-	M	62.0049		2.72	
NO2-	M	46.0055		1.87	
PO4-3	M	94.9714		0.007	
OH-	M	17.0073		4.00	
TOC	M	12.011		0.3189	
TIC	g/L	12.011			
SPG	g/mL			1.464	
TotSolids	wt%				
pH					
3H	uCi/L				
14C	uCi/L				
54Mn	uCi/L				
59Mn	uCi/L				
60Co	uCi/L				
63Ni	uCi/L				
79Se	uCi/L				
90Sr	uCi/L			1270	1019
94Nb	uCi/L				
95Nb	uCi/L				
99Tc	uCi/L				
103Ru	uCi/L				
106RuRh	uCi/L				
113Sn	uCi/L				
129I	uCi/L				
134Cs	uCi/L				
137Cs	uCi/L			624000	504603
144CePr	uCi/L				
154Eu	uCi/L				
155Eu	uCi/L				
226Ra	uCi/L				

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-1 continued.

Evap Camp. 84-3 Analyses				Sample	Decay to
07/03			<	R9991	Oct-93
Component	Units	MW			
234U	uCi/L				
235U	uCi/L				
238U	uCi/L				
237Np	uCi/L				
238Pu	uCi/L				
239/240Pu	uCi/L			10,422	
241Am	uCi/L			11400	
242Cm	uCi/L				
243Cm	uCi/L				
244Cm	uCi/L				
TB	uCi/L				
AT	uCi/L				
Note: Pu (total) assumed to be 239					

WHC-SD-WM-TI-528, Rev. 1

TABLE 3-2: Evaporator Campaign 84-5 Analysis Data⁴

Evap Camp. 84-5 Analyses				Sample				
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	MW						
Ag	ppm	107.868						
Al	M	25.98154		1.3	1.39	1.21	1.25	1.11
As	ppm	74.9216						
B	ppm	10.81						
Ba	ppm	137.33						
Be	ppm	9.01218						
Bi	ppm	208.9804						
Ca	ppm	40.08						
Cd	ppm	112.41						
Ce	ppm	140.12						
Cr	ppm	51.996						
Cu	ppm	63.546						
Fe	ppm	55.847						
Hg	ppm	200.59						
K	ppm	39.0983		0.154	0.178	0.408	0.385	0.11
La	ppm	138.9055						
Li	ppm	6.941						
Mg	ppm	24.305						
Mn	ppm	54.938						
Mo	ppm	95.94						
Na	M	22.98977		14.35		11.48	11.53	10.64
Ni	ppm	58.69						
P	ppm	30.97376						
Pb	ppm	207.2						
Pd	ppm	106.4						
Sb	ppm	121.75						
Se	ppm	78.96						
Si	ppm	28.0855						
Sn	ppm	118.69						
Ta	ppm	180.9479						
Ti	ppm	47.88						
U	g/L	238.029						
V	ppm	50.9415						
W	ppm	183.85						
Zn	ppm	65.38						

4

Reference: SD-WM-PE-022

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-2 continued.

Evap Camp. 84-5 Analyses				Sample				
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	MW						
Zr	ppm	91.22						
CN-	ppm	26.0177						
S-2	ppm	32.06						
NH4+	M	18.0383						
NH3	M	17.0304	<	0.005				
CO3-2	M	60.0092		0.255	0.18	0.94	0.588	0.66
Cl-	M	35.453	<	0.215		0.2	0.23	0.187
F-	M	18.9984	<					
SO4-2	M	96.0576	<					0.078
NO3-	M	62.0049		2.88	2.31	4.09	3.14	3.4
NO2-	M	46.0055		1.97	2.16	1.31	2.05	1.64
PO4-3	M	94.97136		0.02	0.022	0.055	0.026	0.052
OH-	M	17.0073		4.6	4.72	3.84	4.35	3.37
TOC	M	12.011		6.6	5.95	4.31	6.01	4.72
TIC	g/L	12.011						
SPG	g/mL			1.49	1.54	1.52	1.51	1.47
TotSolids	wt%							
pH								
3H	uCi/L							
14C	uCi/L							
54Mn	uCi/L							
55Mn	uCi/L							
59Co	uCi/L							
53Ni	uCi/L							
79Se	uCi/L							
90Sr	uCi/L			17100	9710	21600	18000	11000
94Nb	uCi/L							
95Nb	uCi/L							
99Tc	uCi/L							
103Ru	uCi/L							
106Ru	uCi/L							
113Sn	uCi/L							
129I	uCi/L							
134Cs	uCi/L			1260				
137Cs	uCi/L			940000	1890000	783000	989000	665000
144CePr	uCi/L							
154Eu	uCi/L							
155Eu	uCi/L							
226Ra	uCi/L							

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-2 continued.

Evap Camp. 84-5 Analyses				Sample				
15-Oct-84			<	R3303	R3305	R3307	R3413	R3415
Component	Units	HW						
234U	uCi/L							
235U	uCi/L							
238U	uCi/L							
237Np	uCi/L							
238Pu	uCi/L							
239/240Pu	uCi/L							
241Am	uCi/L							
242Cm	uCi/L							
243Cm	uCi/L							
244Cm	uCi/L							
TB	uCi/L							
AT	uCi/L							

WHC-SD-WM-TI-528, Rev. 1

TABLE 3-3: Evaporator Campaign 85-3 Analysis Data⁵

Evap Camp. 85-3 Analyses				Sample				
03-Apr-85			<	R4680	R4681	R4683	R4684	R4687
Component	Units	MW						
Ag	ppm	107.868						
Al	M	26.98154		1.7		1.8		1.73
As	ppm	74.9216						
B	ppm	10.81						
Ba	ppm	137.33						
Be	ppm	9.01218						
Bi	ppm	208.9804						
Ca	ppm	40.08						
Cd	ppm	112.41						
Ce	ppm	140.12						
Cr	ppm	51.996						
Cu	ppm	63.546						
Fe	ppm	55.847						
Hg	ppm	200.59						
K	ppm	39.0983		0.14		0.18		0.15
La	ppm	138.9055						
Li	ppm	6.941						
Mg	ppm	24.305						
Mn	ppm	54.938						
Mo	ppm	95.94						
Na	M	22.98977		11.45		11.38		13.08
Ni	ppm	58.69						
P	ppm	30.97376						
Pb	ppm	207.2						
Pd	ppm	106.42						
Sb	ppm	121.75						
Se	ppm	78.96						
Si	ppm	28.0855						
Sn	ppm	118.71						
Ta	ppm	180.9479						
Ti	ppm	47.88						
V	g/L	50.9415						
W	ppm	183.84						
Zn	ppm	65.38						

⁵

Reference: SD-WM-PE-023

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-3 continued.

Evap Camo. 85-3 Analyses				Sample				
03-Apr-85			<	R4680	R4681	R4683	R4684	R4687
Component	Units	MW						
Zr	ppm	91.22						
CH-	ppm	26.0177						
S-2	ppm	32.06						
NH4+	M	18.0383						
NH3	M	17.0304	<			0.02		0.02
CO3-2	M	60.0092		0.7		0.14		0.25
Cl-	M	35.453		0.28		0.24		0.2
F-	M	18.9984	<					
SO4-2	M	96.0576	<					
NO3-	M	62.0049		4.18		2.13		3.05
NO2-	M	46.0055		2.42		2.28		3.13
PO4-3	M	94.97136		0.03		0.01		0.02
OH-	M	17.0073		3.05		4.48		3.38
TOC	M	12.011		4.1		5.3		2.23
TIC	g/L	12.011						
SPG	g/mL			1.53		1.5		1.48
TotSolids	wt%							
pH				13.5				
3H	uCi/L							
14C	uCi/L							
54Mn	uCi/L							
59Mn	uCi/L							
50Co	uCi/L							
53Ni	uCi/L							
79Se	uCi/L							
90Sr	uCi/L			3950				
94Nb	uCi/L							
95Nb	uCi/L							
99Tc	uCi/L							
103Ru	uCi/L							
106RuRh	uCi/L							
113Sn	uCi/L							
129I	uCi/L							
134Cs	uCi/L							
137Cs	uCi/L			513000				
144CePr	uCi/L							
154Eu	uCi/L							
155Eu	uCi/L							
226Ra	uCi/L							

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-3 continued.

Evap Camp. 85-3 Analyses				Sample				
03-Apr-85			<	R4580	R4581	R4583	R4584	R4587
Component	Units	HW						
234U	uCi/L							
235U	uCi/L							
238U	uCi/L							
237Np	uCi/L							
238Pu	uCi/L							
239/240Pu	uCi/L							
241Am	uCi/L							
242Cm	uCi/L							
243Cm	uCi/L							
244Cm	uCi/L							
TB	uCi/L							
AT	uCi/L							

WHC-SD-WM-TI-528, Rev. 1

TABLE 3-4: Evaporator Campaign 84-5 Analysis Summary

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
Ag	ppm	0				
Al	M	5		1.252	0.104019	
As	ppm	0				
B	ppm	0				
Ba	ppm	0				
Be	ppm	0				
Bi	ppm	0				
Ca	ppm	0				
Cd	ppm	0				
Ce	ppm	0				
Cr	ppm	0				
Cu	ppm	0				
Fe	ppm	0				
Hg	ppm	0				
K	ppm	5		0.187	0.128787	
La	ppm	0				
Li	ppm	0				
Mg	ppm	0				
Mn	ppm	0				
Mo	ppm	0				
Na	M	4		12	1.618991	
Nd	ppm	0				
Ni	ppm	0				
P	ppm	0				
Pb	ppm	0				
Pd	ppm	0				
Sb	ppm	0				
Se	ppm	0				
Si	ppm	0				
Sr	ppm	0				
Ta	ppm	0				
Ti	ppm	0				
V	g/L	0				
V	ppm	0				
W	ppm	0				
Zn	ppm	0				
Zr	ppm	0				
CN-	ppm	0				

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-4 continued.

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
S-2	ppm	0				
NH4+	M	0				
NH3	M	1		0.005		
CO3-2	M	5		0.5246	0.310783	
Cl-	M	4		0.298	0.018601	
F-	M	0				
SO4-2	M	1		0.078		
NO3-	M	5		3.164	0.656453	
NO2-	M	5		1.825	0.347606	
PO4-3	M	5		0.035	0.017059	
OH-	M	5		4.176	0.563143	
TOC	g/L	5		5.518	0.961182	
TIC	g/L	0				
SPG	g/mL	5		1.506	0.027019	
TotSolids	wt%	0				
pH		0				
3H	uCi/L	0				
14C	uCi/L	0				
54Mn	uCi/L	0				
59Mn	uCi/L	0				
50Co	uCi/L	0				
53Ni	uCi/L	0				
79Se	uCi/L	0				
90Sr	uCi/L	5		15482	4994.809	12506 79
94Nb	uCi/L	0				
95Nb	uCi/L	0				
99Tc	uCi/L	0				
103Ru	uCi/L	0				
106RuRh	uCi/L	0				
113Sn	uCi/L	0				
129I	uCi/L	0				
134Cs	uCi/L	0		1250		52 27367
137Cs	uCi/L	5		1033400	490346.1	841151 3
144CePr	uCi/L	0				
154Eu	uCi/L	0				
155Eu	uCi/L	0				
226Ra	uCi/L	0				
234U	uCi/L	0				
235U	uCi/L	0				

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-4 continued.

Evap Camp. 84-5 Analyses						
Oct-84						Oct-93
Component	Units	n	<	Mean	S.Dev.	
238U	uCi/L	0				
237Np	uCi/L	0				
238Pu	uCi/L	0				
239/240Pu	uCi/L	0				
241Am	uCi/L	0				
242Cm	uCi/L	0				
243Cm	uCi/L	0				
244Cm	uCi/L	0				
TB	uCi/L	0				
AT	uCi/L	0				

WHC-SD-WM-TI-528, Rev. 1

TABLE 3-5: Evaporator Campaign 85-3 Analysis Summary

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
Ag	ppm	0				
Al	M	3		1.743333	0.051316	
As	ppm	0				
B	ppm	0				
Ba	ppm	0				
Be	ppm	0				
Bi	ppm	0				
Ca	ppm	0				
Cd	ppm	0				
Ce	ppm	0				
Cr	ppm	0				
Cu	ppm	0				
Fe	ppm	0				
Hg	ppm	0				
K	ppm	3		0.156667	0.020817	
La	ppm	0				
Li	ppm	0				
Mg	ppm	0				
Mn	ppm	0				
Mo	ppm	3				
Na	M	3		11.97	0.961925	
Nd	ppm	0				
Ni	ppm	0				
P	ppm	0				
Pb	ppm	0				
Pd	ppm	0				
Sb	ppm	0				
Se	ppm	0				
Si	ppm	0				
Sn	ppm	0				
Ta	ppm	0				
Ti	ppm	0				
U	g/L	0				
V	ppm	0				
W	ppm	0				
Zn	ppm	0				
Zr	ppm	0				
CN-	ppm	0				

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-5 continued.

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
S-2	ppm	0				
NH4+	M	0				
NH3	M	2		0.02	7.09e-11	
CO3-2	M	3		0.363333	0.296704	
Cl-	M	3		0.24	0.04	
F-	M	0				
SO4-2	M	0				
NO3-	M	3		3.12	1.026791	
NO2-	M	3		2.61	0.455741	
PO4-3	M	3		0.02	0.01	
OH-	M	3		3.636667	0.748755	
TOC	M	3		3.876667	1.547137	
TIC	g/L	0				
SPG	g/mL	3		1.503333	0.025166	
TotSolids	wt%	0				
pH		1		13.5		
3H	uCi/L	0				
14C	uCi/L	0				
54Mn	uCi/L	0				
59Mn	uCi/L	0				
60Co	uCi/L	0				
63Ni	uCi/L	0				
79Se	uCi/L	0				
90Sr	uCi/L	0		3950		3226 485
94Nb	uCi/L	0				
95Nb	uCi/L	0				
99Tc	uCi/L	0				
103Ru	uCi/L	0				
106RuRh	uCi/L	0				
113Sn	uCi/L	0				
129I	uCi/L	0				
134Cs	uCi/L	0				
137Cs	uCi/L	0		613000		504323 5
144CePr	uCi/L	0				
154Eu	uCi/L	0				
155Eu	uCi/L	0				
226Ra	uCi/L	0				
234U	uCi/L	0				
235U	uCi/L	0				

WHC-SD-WM-TI-528, Rev. 1
TABLE 3-5 continued.

Evap Camp. 85-3 Analyses						Decay to
Apr-85						Oct-93
Component	Units	n	<	Mean	S.Dev.	
238U	uCi/L	0				
237Np	uCi/L	0				
238Pu	uCi/L	0				
239/240Pu	uCi/L	0				
241Am	uCi/L	0				
242Cm	uCi/L	0				
243Cm	uCi/L	0				
244Cm	uCi/L	0				
TB	uCi/L	0				
AT	uCi/L	0				

WHC-SD-WM-TI-528, Rev. 1

TABLE 4-1: Concentrated Waste Summary Data - 101AW, 103AN⁶

Units: Molarity: uCi/L for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AN Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
Ag	M	3.09e-04	3.09e-04	mg/g	1.00e-02	1.48e-04
Al	M	1.03e+00	1.03e+00	mg/g	3.60e+01	2.13e+00
As	M	1.33e-07	1.33e-07	mg/g	1.00e-01	2.14e-03
B	M			mg/g		
Ba	M	6.80e-05	6.80e-05	mg/g	1.00e-02	1.17e-04
Be	M			mg/g	1.00e-02	1.78e-03
Bi	M	5.79e-04	5.79e-04	mg/g	3.00e-02	2.30e-04
Ca	M	8.26e-04	8.26e-04	mg/g	5.40e-02	2.16e-03
Cd	M	1.08e-05	1.08e-05	mg/g	1.00e-02	1.42e-04
Ce	M			mg/g		
Cr	M	3.09e-03	3.09e-03	mg/g	5.30e-01	1.63e-02
Cu	M	3.81e-04	3.81e-04	mg/g	7.50e-03	1.89e-04
Fe	M	7.86e-04	7.86e-04	mg/g	4.40e-02	1.26e-03
Hg	mg/L	1.57e-01	7.82e-07	mg/g	1.00e-02	7.98e-05
K	M	1.07e+00	1.07e+00	mg/g	9.50e+00	3.89e-01
La	M			mg/g		
Li	M			mg/g		
Mg	M	2.16e-03	2.16e-03	mg/g	1.80e-02	1.18e-03
Mn	M	4.75e-04	4.75e-04	mg/g	1.80e-02	5.24e-04
Mo	M	5.00e-04	5.00e-04	mg/g	5.50e-02	9.17e-04
Na	M	1.30e+01	1.30e+01	mg/g	2.10e-02	1.46e+01
Nd	M			mg/g		
Ni	M			mg/g	1.50e-02	4.09e-04
P	M			mg/g		
Pb	M	1.46e-03	1.46e-03	mg/g	4.50e-02	3.47e-04
Pd	M			mg/g		
Sb	M			mg/g	1.00e-01	1.31e-03
Se	M	4.20e-07	4.20e-07	mg/g	1.30e-01	2.63e-03
Si	M	4.26e-03	4.26e-03	mg/g	1.70e-01	9.68e-03
Sn	M			mg/g		
Ta	M			mg/g		
Ti	M	9.88e-05	9.88e-05	mg/g	1.00e-02	3.34e-04
U	M	9.39e-04	9.39e-04	mg/g	7.70e-02	5.18e-04
V	M			mg/g	1.00e-02	3.14e-04

6

References: WHC-SD-WM-TRP-055 and SD-WM-TI-355, Rev. 1. Less-thans calculated as real values.

WHC-SD-WM-TI-528, Rev. 1
TABLE 4-1 continued.

Units: Molarity: uCi/L for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AN Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
W	M			mg/g	1.30e-01	1.13e-03
Zn	M	4.84e-03	4.84e-03	mg/g	3.00e-02	7.34e-04
Zr	M	5.54e-04	5.54e-04	mg/g	1.50e-02	2.63e-04
CN-	M	1.03e-03	1.03e-03	mg/g	2.10e-02	1.29e-03
S-2	M			mg/g		
NH4+	M	1.45e-02	1.45e-02	mg/g		
NH3	M			mg/g		
CO3-2	M	2.05e-01	2.05e-01	mg/g	5.60e+00	1.49e-01
Cl-	M	1.46e-01	1.46e-01	mg/g	6.00e+00	2.71e-01
F-	M	4.02e-03	4.02e-03	mg/g	4.50e-01	3.87e-02
SO4-2	M	1.07e-02	1.07e-02	mg/g	1.00e+00	1.67e-02
NO3-	M	3.46e+00	3.46e+00	mg/g	1.00e+02	2.58e+00
NO2-	M	2.19e+00	2.19e+00	mg/g	8.60e+01	2.99e+00
PO4-3	M	2.22e-02	2.22e-02	mg/g	5.80e-01	9.77e-03
OH-	M	5.07e+00	5.07e+00	mg/g	6.10e+01	5.74e+00
TOC g/L	g/L	2.46e+00	2.46e+00	mg/g	4.60e+00	6.13e-01
TTC g/L	g/L	2.46e+00	2.46e+00	mg/g		
SPG	g/cm3	1.56e-03	1.56e-03	g/cm3	1.50e+00	1.50e+00
TotSolids	wt%					
CH						
CH	uCi/L	3.07e-00	3.07e-00	Ci/L	4.00e-06	4.00e-00
C-14	uCi/L	3.70e-01	3.70e-01	Ci/L	2.00e-06	2.00e-00
54Mn	uCi/L			Ci/L		
59Mn	uCi/L			Ci/L		
60Co	uCi/L	2.96e-01	2.96e-01	Ci/L	3.80e-05	3.80e-01
63Ni	uCi/L			Ci/L		
79Se	uCi/L	4.80e-01	4.80e-01	Ci/L	4.30e-05	4.30e-01
89-90Sr	uCi/L	1.09e-03	1.09e-03	Ci/L	1.30e-02	1.30e-04
90Y	uCi/L	6.82e-01	6.82e-01	Ci/L	7.00e-06	7.00e-00
105Nb	uCi/L			Ci/L		
99Tc	uCi/L	1.52e-02	1.52e-02	Ci/L	1.70e-04	1.70e-02
103Ru	uCi/L			Ci/L		
106RuRh	uCi/L	3.70e-03	3.70e-03	Ci/L	6.80e-05	6.80e-01
113Sn	uCi/L			Ci/L		
129I	uCi/L	3.03e-01	3.03e-01	Ci/L	5.20e-07	5.20e-01
134Cs	uCi/L	1.53e-03	1.53e-03	Ci/L	1.00e-04	1.00e-02
137Cs	uCi/L	5.20e-05	5.20e-05	Ci/L	7.50e-01	7.50e-05
144CePr	uCi/L			Ci/L		

WHC-SD-WM-TI-528, Rev. 1
TABLE 4-1 continued.

Units: Molarity: $\mu\text{Ci/L}$ for radionuclides; others as noted						
	101-AW Analysis		Jul-90	103-AW Analysis		Dec-84
			Uniform			Uniform
Component	Units	MEAN	Unit mean	Units	MEAN	Unit mean
154Eu	$\mu\text{Ci/L}$			Ci/L		
155Eu	$\mu\text{Ci/L}$			Ci/L		
226Ra	$\mu\text{Ci/L}$			Ci/L		
234U	$\mu\text{Ci/L}$			Ci/L	5.30e-08	5.30e-02
235U	$\mu\text{Ci/L}$			Ci/L	1.10e-09	1.10e-03
238U	$\mu\text{Ci/L}$			Ci/L	1.40e-08	1.40e-02
237Nd	g/L	3.06e-03	2.16e+00	Ci/L	2.00e-08	2.00e-02
238Pu	$\mu\text{Ci/L}$			Ci/L	9.80e-07	9.80e-01
239/240Pu	$\mu\text{Ci/L}$	1.15e+00	1.15e+00	Ci/L	1.90e-06	1.90e+00
241Am	$\mu\text{Ci/L}$	1.20e+00	1.20e+00	Ci/L	2.30e-06	2.30e+00
242Cm	$\mu\text{Ci/L}$			Ci/L		
243/244Cm	$\mu\text{Ci/L}$	5.33e-02	5.33e-02	Ci/L		
244Cm	$\mu\text{Ci/L}$			Ci/L	4.20e-07	4.20e-01
TB	$\mu\text{Ci/L}$			Ci/L		
AT	$\mu\text{Ci/L}$			Ci/L		
Volume	L		3.83e+06			3.49e+06

WHC-SD-WM-TI-528, Rev. 1

TABLE 4-2: Concentrated Waste Summary Data - 105AP, 106AN⁷

	Less-thans calculated as real values						
	105-AP Estimate		Jan-89		106-AN Analysis		Apr-89
		Top	Bottom	Uniform			Uniform
	Units	MEAN	MEAN	Unit mean	Units	MEAN	Unit mean
Ag	M	9.30e-05	2.80e-04	2.00e-04	mg/L	3.63e+00	3.37e-05
Al	M	2.80e-01	7.10e-02	1.60e-01	mg/L	9.28e+03	3.44e-01
As	M	4.00e-08	1.20e-07	8.58e-08	mg/L	7.20e-02	9.61e-07
B	M				mg/L		
Ba	M	2.00e-05	6.10e-05	4.35e-05	mg/L	1.11e+01	8.08e-05
Be	M				mg/L		
Bi	M	1.70e-04	5.20e-04	3.70e-04	mg/L	1.45e+02	5.94e-04
Ca	M	2.50e-04	1.70e-03	1.08e-03	mg/L	9.02e+01	2.25e-03
Cd	M	3.20e-06	9.70e-06	6.92e-06	mg/L	4.96e+01	4.41e-04
Ce	M				mg/L		
Cr	M	9.30e-04	5.10e-03	3.32e-03	mg/L	5.64e+02	1.08e-02
Cu	M	1.10e-04	3.40e-04	2.42e-04	mg/L	3.75e+00	5.90e-05
Fe	M	2.40e-04	1.70e-04	2.00e-04	mg/L	6.90e+00	1.24e-04
Hg	M	2.30e-07	7.00e-07	4.99e-07	mg/L	5.00e-02	2.49e-07
K	M	7.20e-01	9.60e-01	8.57e-01	mg/L	1.08e+03	2.76e-02
La	M				mg/L		
Li	M				mg/L		
Mg	M	6.50e-04	3.50e-04	4.95e-04	mg/L	2.78e+00	1.24e-04
Mn	M	1.40e-04	4.30e-04	3.06e-04	mg/L	5.57e+01	1.01e-03
Mo	M	1.80e-04	5.40e-04	3.86e-04	mg/L	6.66e+01	6.94e-04
Na	M	2.80e-02	9.30e-02	6.35e-02	mg/L	9.33e+04	3.93e+00
Ni	M				mg/L		
Ni	M	1.00e-03	3.30e-03	2.15e-03	mg/L		
P	M	6.70e-03	2.30e-02	1.43e-02	mg/L	5.11e+03	1.97e-01
Pb	M	4.40e-04	1.30e-03	9.33e-04	mg/L	4.60e+02	2.22e-03
Pd	M				mg/L		
Se	M				mg/L		
Te	M	1.30e-07	7.60e-07	2.73e-07	mg/L	1.34e-01	1.70e-06
Ti	M	1.30e-03	1.30e-03	1.53e-03	mg/L		
Sn	M				mg/L		
Ta	M				mg/L	1.30e-01	7.18e-07
Th	M	3.00e-05	8.30e-05	6.38e-05	mg/L	3.51e+00	7.33e-05
U	M	2.80e-04	8.60e-04	6.06e-04	mg/L	4.00e-03	1.68e-05
V	M				mg/L		

References: WHC-SD-WM-TP-130, WHC-SD-WM-TP-065, and SD-WM-TI-355, Rev. 1.

WHC-SD-WM-TI-528, Rev. 1
TABLE 4-2 continued.

Less-thans calculated as real values							
105-AP Estimate				Jan-89	106-AN Analysis		Apr-89
	Top	Bottom	Uniform				Uniform
Units	MEAN	MEAN	Unit mean	Units	MEAN		Unit mean
W	M			mg/L			
Zn	M	1.50e-03	9.00e-04	1.15e-03	mg/L	9.44e+00	1.44e-04
Zr	M	1.70e-04	5.00e-04	3.55e-04	mg/L	2.78e+01	3.05e-04
CN-	M	3.10e-04	9.30e-04	6.55e-04	g/L	6.00e-03	2.31e-04
S-2	M			mg/L			
NH4+	M	5.30e-03	1.40e-04	2.34e-03	mg/L	1.30e+02	7.22e-03
NH3	M			mg/L			
CO3-2	M	2.70e-01	2.40e-01	2.55e-01	M	3.27e-01	3.27e-01
Cl-	M	3.90e-02	9.80e-02	7.22e-02	mg/L	2.46e+03	6.94e-02
F-	M	1.70e-01	1.00e-01	1.35e-01	mg/L	5.16e+01	3.24e-03
SO4-2	M	3.40e-02	1.80e-02	2.42e-02	mg/L	2.15e+03	2.24e-02
NO3-	M	1.80e+00	3.30e+00	2.55e+00	mg/L	6.85e+04	1.10e+00
NO2-	M	5.40e-01	1.50e+00	1.09e+00	M	6.44e-01	6.44e-01
PO4-3	M	2.50e-02	9.70e-03	1.52e-02	mg/L	1.84e+04	1.94e-01
OH-	M	3.20e+00	5.70e+00	4.53e+00	M	4.74e-01	4.74e-01
TOC g/L	g/L	2.20e+00	5.20e+00	3.92e+00	g/L	3.26e+00	3.26e+00
TC g/L	g/L			g/L			
SPG	g/cm3	1.25e+00	1.42e+00	1.35e+00	g/cm3	1.23e+00	1.23e+00
TotSolids	wt%			wt%			
pH							
3H	uCi/L	1.10e-01	3.50e-03	3.55e-03	uCi/L	3.44e+00	3.44e+00
14C	uCi/L	1.10e-01	3.30e-01	2.35e-01	uCi/L	3.35e-01	3.35e-01
54Mn	uCi/L				uCi/L		
59Mn	uCi/L				uCi/L		
60Co	uCi/L	8.90e-00	2.70e-01	1.92e-01	uCi/L	9.15e-00	9.15e-00
63Ni	uCi/L				uCi/L		
79Se	uCi/L	1.40e-01	4.30e-01	3.26e-01	uCi/L	2.40e-01	2.40e-01
89/90Sr	uCi/L	3.10e-02	1.40e-02	2.15e-02	uCi/L	2.23e+03	2.23e+03
94Nb	uCi/L	2.30e-01	5.10e-01	4.35e-01	uCi/L	2.30e-01	2.30e-01
95Nb	uCi/L				uCi/L		
99Tc	uCi/L	3.30e-03	2.50e-01	1.75e-01	uCi/L	5.32e-01	6.92e-01
103Ru	uCi/L				uCi/L		
106RuRh	uCi/L	1.10e-03	3.20e-03	2.35e-03	uCi/L	1.39e+03	1.39e+03
113Sn	uCi/L				uCi/L		
129I	uCi/L	2.30e-02	5.30e-02	4.15e-02	uCi/L	7.50e-02	7.50e-02
134Cs	uCi/L	1.50e-03	3.20e-03	2.52e-03	uCi/L	2.37e+01	2.37e+01
137Cs	uCi/L	1.70e-05	3.70e-05	2.35e-05	uCi/L	2.05e+05	2.05e+05
144CePr	uCi/L				uCi/L		

WHC-SD-WM-TI-528, Rev. 1
TABLE 4-2 continued.

	Less-thans calculated as real values						
	105-AP Estimate			Jan-89	106-AN Analysis		Apr-89
		Top	Bottom	Uniform			Uniform
	Units	MEAN	MEAN	Unit mean	Units	MEAN	Unit mean
154Eu	uCi/L				uCi/L		
155Eu	uCi/L				uCi/L		
226Ra	uCi/L				uCi/L		
234U	uCi/L				uCi/L		
235U	uCi/L				uCi/L		
238U	uCi/L				uCi/L		
237Nb	uCi/L	7.05e-01	1.90e+00	1.39e+00	g/L	3.00e-03	2.12e+00
238Pu	uCi/L	1.80e-02	5.30e-02	3.80e-02	uCi/L	2.00e-02	2.00e-02
239/240Pu	uCi/L	2.00e-02	5.90e-02	4.23e-02	uCi/L	3.78e-02	3.78e-02
241Am	uCi/L	1.00e+00	1.60e+00	1.34e+00	uCi/L	6.06e-01	6.06e-01
242Cm	uCi/L				uCi/L		
243/244Cm	uCi/L	1.60e-02	4.80e-02	3.43e-02	uCi/L	4.70e-02	4.70e-02
244Cm	uCi/L				uCi/L		
TB	uCi/L				uCi/L		
AT	uCi/L				uCi/L		
Volume	L	1.34e+06	1.80e+06	3.15e+06			3.67e+06

WHC-SD-WM-TI-528, Rev. 1

TABLE 4-3: Concentrated Waste Summary Data - 104AN, 105AN

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
Ag	ppm	107.868					
Al	M	26.98154	1.74e+00	1.25e+00	1.81e+00	1.39e+00	1.74e+00
As	ppm	74.9216					
B	ppm	10.81					
Ba	ppm	137.33					
Be	ppm	9.01218					
Bi	ppm	208.9804					
Ca	ppm	40.08					
Cd	ppm	112.41					
Ce	ppm	140.12					
Cr	ppm	51.996			1.30e-02	1.30e-02	1.30e-02
Cu	ppm	63.546					
Fe	ppm	55.847			2.00e-04	2.00e-04	2.00e-04
Hg	ppm	200.59					
K	ppm	39.0983	1.57e-01	1.87e-01		1.83e-01	1.57e-01
La	ppm	138.9055					
Li	ppm	6.941					
Mg	ppm	24.305					
Mn	ppm	54.938					
Mo	ppm	95.94					
Na	M	22.98977	1.20e+01	1.20e+01		1.20e+01	1.20e+01
Nd	ppm	144.24					
Ni	ppm	58.7					
P	ppm	30.97376					
Pb	ppm	207.2					
Pd	ppm	106.4					
Sb	ppm	121.75					
Se	ppm	78.96					
Si	ppm	28.0855					
Sn	ppm	118.69					
Ta	ppm	180.9479					
Ti	ppm	47.9					
V	g/L	238.029					
V	ppm	50.9415					
W	ppm	183.85					
Zn	ppm	65.38					
Zr	ppm	91.22					
CN-	ppm	26.9177					

WHC-SD-WM-TI-528, Rev. 1
Table 4-3 continued.

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
S-2	opm	32.06					
NH4+	M	18.0383					
NH3	M	17.0304	2.00e-02	5.00e-03		6.99e-03	2.00e-02
CO3-2	M	60.0092	3.63e-01	5.25e-01	2.80e-01	4.72e-01	3.63e-01
Cl-	M	35.453	2.40e-01	2.08e-01		2.12e-01	2.40e-01
F-	M	18.9984					
SO4-2	M	96.0576		7.80e-02	1.60e-02	6.82e-02	6.82e-02
NO3-	M	62.0049	3.12e+00	3.16e+00	2.72e+00	3.10e+00	3.12e+00
NO2-	M	46.0055	2.61e+00	1.83e+00	1.87e+00	1.92e+00	2.61e+00
PO4-3	M	94.97136	2.00e-02	3.50e-02	7.00e-03	2.94e-02	2.00e-02
OH-	M	17.0073	3.64e+00	4.18e+00	4.00e+00	4.09e+00	3.64e+00
TOC	g/L	12.011	4.66e+01	6.63e+01	3.83e+00	5.53e+01	4.66e+01
TIC	g/L	12.011					
SPG	g/mL		1.50e+00	1.51e+00	1.46e+00	1.50e+00	1.50e+00
TotSolids	wt%						
pH			1.35e+01			1.35e+01	1.35e+01
3H	uCi/L						
14C	uCi/L						
54Mn	uCi/L						
59Mn	uCi/L						
50Co	uCi/L						
53Ni	uCi/L						
79Se	uCi/L						
90Sr	uCi/L		3.95e-03	1.55e-04	1.27e-03	1.20e-04	3.95e-03
94Nb	uCi/L						
95Nb	uCi/L						
99Tc	uCi/L						
103Ru	uCi/L						
106RuRh	uCi/L						
113Sn	uCi/L						
129I	uCi/L						
134Cs	uCi/L			1.26e-03		1.08e-03	1.38e-03
137Cs	uCi/L		6.13e-05	1.03e-06	5.24e-05	9.18e-05	6.13e-05
144CePr	uCi/L						
154Eu	uCi/L						
155Eu	uCi/L						
226Ra	uCi/L						
234U	uCi/L						
235U	uCi/L						

WHC-SD-WM-TI-528, Rev. 1
Table 4-3 continued.

104AN and 105AN			85-3	84-5	84-3	Apr-85	Apr-85
Estimates			Apr-85	Oct-84	Jul-84	104-AN	105-AN
Component	Units	MW					
238U	uCi/L						
237Np	uCi/L						
238Pu	uCi/L						
239/240Pu	uCi/L				1.04e+01	1.04e+01	1.04e+01
241Am	uCi/L				1.14e+04	1.14e+04	1.14e+04
242Cm	uCi/L						
243Cm	uCi/L						
244Cm	uCi/L						
TB	uCi/L						
AT	uCi/L						
Volume	L		4.58e+05	2.99e+06	5.62e+05	4.01e+06	3.68e+06

WHC-SD-WM-TI-528, Rev. 1

TABLE 5-1: Radioisotope Decay Data⁸

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dm/g	Ci/g		
3	H	1.23e+01	y	3.89e+08	2.15e+16	9.66e+03	Beta	3He
14	C	5.73e+03	y	1.81e+11	9.89e+12	4.46e+00	Beta	14N
32	P	1.43e+01	d	1233792	6.34e+17	2.86e+05	Beta	32S
35	S	8.72e+01	d	7534080	9.50e+16	4.28e+04	Beta	35Cl
51	Cr	2.77e+01	d	2393626	2.05e+17	9.24e+04	EC	51V
54	Mn	3.12e+02	d	26974080	1.72e+16	7.74e+03	EC	54Cr
55	Fe	2.73e+00	y	86149889	5.29e+15	2.38e+03	EC	55Mn
59	Fe	4.45e+01	d	3845664	1.10e+17	4.97e+04	Beta	59Co
58	Co	7.09e+01	d	6124032	7.05e+16	3.18e+04	EC	58Fe
60	Co	5.27e+00	y	1.56e+08	2.51e+15	1.13e+03	Beta	60Ni
60	mCo	1.05e+01	m	528.2	6.64e+20	2.99e+08	IT, Beta	60Co (99.75%), 60Ni (0.25%)
59	Ni	7.60e+04	y	2.40e+12	1.77e+11	7.97e-02	EC	59Co
63	Ni	1.00e+02	y	3.15e+09	1.25e+14	5.67e+01	Beta	63Cu
65	Zn	2.44e+02	d	21064320	1.83e+16	8.24e+03	EC	65Cu
67	Ga	3.26e+00	d	281750.4	1.33e+18	5.98e+05	EC	67Zn
75	Se	1.20e+02	d	10348992	3.23e+16	1.45e+04	EC	75As
79	Se	6.50e+04	y	2.35e+12	1.55e+11	6.96e-02	Beta	79Br
85	Kr	1.07e+01	y	3.39e+08	8.70e+14	3.92e+02	Beta	85Rb
86	Rb	1.87e+01	d	1.611360	1.81e+17	8.14e+04	Beta	86Sr
89	Sr	5.05e+01	d	4364928	5.45e+16	2.90e+04	Beta	89Y
90	Sr	2.91e+01	y	9.12e+08	3.33e+14	1.36e+02	Beta	90Y
90	Zr	2.67e+00	d	230774.4	1.21e+18	5.43e+05	Beta	90Zr
91	Y	5.85e+01	d	5055264	5.44e+16	2.45e+04	Beta	91Zr
93	Zr	1.50e+06	y	4.73e+13	5.59e+09	2.56e-03	Beta	93Nb
95	Zr	6.40e+01	d	5531328	4.77e+16	2.15e+04	Beta	95Nb
93	mNb	1.61e+01	y	5.38e+08	5.30e+14	2.39e+02	IT	93Nb
94	Nb	2.00e+04	y	5.31e+11	4.22e+11	1.90e-01	Beta	94Mo
95	Nb	3.50e+01	d	3021408	5.72e+16	3.93e+04	Beta	95Mo
99	Tc	2.13e+05	y	6.72e+12	3.76e+10	1.70e-02	Beta	99Ru
99	mTc	6.31e+00	n	21521.6	1.17e+19	5.27e+06	IT	99Tc
103	Ru	3.93e+01	d	3392928	7.17e+16	3.23e+04	Beta	103Rh
106	Ru	1.02e+00	y	32187871	7.34e+15	3.31e+03	Beta	106Rh
103	mRh	5.51e+01	n	3357.2	7.22e+19	3.25e+07	IT	103Rh

8

Reference: Walker et al., 1989

A-67

WHC-SD-WM-TI-528, Rev. 1
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	Ci/g		
106	Rh	2.18e+00	h	7848	3.01e+19	1.36e+07	Beta	106Pd
107	Pd	6.50e+06	y	2.05e+14	1.14e+09	5.14e-04	Beta	107Ag
110	Ag	2.46e+01	s	24.6	9.25e+21	4.17e+09	Beta.EC	110Cd (99.7%), 110Pd (0.3%)
110	mAg	2.50e+02	d	21582720	1.05e+16	4.75e+03	Beta.IT	110Cd (98.64%), 110Ag (1.36%)
113	mCd	1.41e+01	y	4.45e+08	4.98e+14	2.24e+02	Beta.IT	113In (99.9%), 113Cd (0.1%)
115	mCd	4.46e+01	d	3853440	5.65e+16	2.55e+04	Beta	115In
113	mIn	1.66e+00	h	5968.8	3.71e+19	1.67e+07	IT	113In
114	mIn	4.95e+01	d	4277664	5.14e+16	2.31e+04	IT.EC	114In (95.7%), 14Cd (4.3%)
113	Sn	1.15e+02	d	9944640	2.23e+16	1.00e+04	EC	113In
117	mSn	1.36e+01	d	1175904	1.82e+17	8.20e+04	IT	117Sn
119	mSn	2.93e+02	d	25315200	8.31e+15	3.74e+03	IT	119Sn
121	mSn	5.50e+01	y	1.74e+09	1.19e+14	5.37e+01	IT.Beta	121Sn (77.6%), 121Sb (22.4%)
123	Sn	1.29e+02	d	11162880	1.82e+16	8.22e+03	Beta	123Sb
125	Sn	9.63e+00	d	832032	2.41e+17	1.08e+05	Beta	125Sb
126	Sn	1.00e+05	y	3.16e+12	6.30e+10	2.84e-02	Beta	126Sb
124	Sb	6.02e+01	d	5201280	3.88e+16	1.75e+04	Beta	124Te
125	Sb	2.76e+00	y	87033478	2.30e+15	1.04e+03	Beta	125Te
126	Sb	1.24e+01	d	1071360	1.86e+17	8.36e+04	Beta	126Te
126	mSb	1.90e+01	m	1140	1.74e+20	7.85e+07	Beta.IT	125Te (86%), 126Se (14%)
123	mTe	1.20e+02	d	10342080	1.97e+16	8.87e+03	IT	123Te
125	mTe	5.80e+01	d	5011200	4.00e+16	1.80e+04	IT	125Te
127	Te	9.40e+00	h	33840	5.93e+18	2.62e+06	Beta	127I
127	mTe	1.09e+02	d	9417600	2.09e+16	9.43e+03	IT.Beta	127Te (97.6%), 127I (2.4%)
129	Te	1.16e+00	h	4176	4.65e+19	2.09e+07	Beta	129I
129	mTe	3.36e+01	d	2903040	6.69e+16	3.01e+04	IT.Beta	129Te (64%), 129I (36%)
125	I	6.01e+01	d	5195096	3.96e+16	1.74e+04	EC	125Te
129	I	1.57e+07	y	4.95e+14	3.92e+08	1.76e-04	Beta	129Xe
131	I	8.04e+00	d	694656	2.75e+17	1.24e+05	Beta	130Xe
133	Te	5.24e+00	d	452996	4.16e+17	1.37e+05	Beta	133Cs
134	Cs	2.07e+00	y	65164660	2.87e+15	1.29e+03	Beta	134Ba
135	Cs	2.30e+06	y	7.26e+13	2.55e+09	1.15e-03	Beta	135Ba
137	Cs	3.02e+01	y	9.52e+08	1.92e+14	8.65e-01	Beta	137mBa 137Ba
137	mBa	2.55e+00	m	153.12	1.19e+21	5.38e+08	IT	137Ba
141	Ce	3.25e+01	d	2808000	6.32e+16	2.85e+04	Beta	141Pr
144	Ce	2.85e+02	d	24589440	7.07e+15	3.19e+03	Beta	144Pr
143	Pr	1.36e+01	d	1172448	1.49e+17	6.73e+04	Beta	143Nd

WHC-SD-WM-TI-528, Rev. 1
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	CI/g		
144	Pr	1.73e+01	m	1036.8	1.68e+20	7.56e+07	Beta	144Nd
144	mPr	7.20e+00	m	432	4.03e+20	1.81e+08	IT, Beta	144Pr (99.96%), 144Nd (0.04%)
146	Pm	5.53e+00	y	1.75e+08	9.83e+14	4.43e+02	EC, Beta	146Nd (66.1%), 146Sm (33.9%)
147	Pm	2.62e+00	y	82785941	2.06e+15	9.27e+02	Beta	147Sm
148	Pm	5.37e+00	d	463968	3.65e+17	1.64e+05	Beta	148Sm
148	mPm	4.13e+01	d	3567456	4.74e+16	2.14e+04	Beta, IT	148Sm (95.4%), 148Pm (4.6%)
151	Sm	9.00e+01	y	2.84e+09	5.84e+13	2.63e+01	Beta	151Eu
152	Eu	1.35e+01	y	4.25e+08	3.87e+14	1.74e+02	EC, Beta	152Sm (72.08%), 152Gd (27.92%)
154	Eu	8.59e+00	y	2.71e+08	6.00e+14	2.70e+02	Beta	154Gd
155	Eu	4.71e+00	y	1.49e+08	1.09e+15	4.90e+02	Beta	155Gd
153	Gd	2.42e+02	d	20874240	7.84e+15	3.53e+03	EC	153Eu
160	Tb	7.23e+01	d	6246720	2.51e+16	1.13e+04	Beta	160Dy
192	Ir	7.38e+01	d	6378912	2.04e+16	9.21e+03	Beta, EC	192Pt (95.4%), 192Os (4.6%)
201	Tl	3.04e+00	d	262483.2	4.75e+17	2.14e+05	EC	201Hg
207	Tl	4.77e+00	m	286.2	4.23e+20	1.90e+08	Beta	207Pb
208	Tl	3.05e+00	m	183.18	6.57e+20	2.96e+08	Beta	208Pb
209	Pb	3.25e+00	h	11710.8	1.02e+19	4.61e+06	Beta	209Bi
211	Pb	3.61e+01	m	2156	5.48e+19	2.47e+07	Beta	211Bi
212	Pb	1.06e+01	h	38304	3.08e+18	1.39e+06	Beta	212Bi
211	Bi	2.14e+00	m	128.4	9.24e+20	4.16e+08	Alpha, Beta	207Tl (99.72%), 211Po (0.273%)
212	Bi	1.01e+00	n	3532.4	3.35e+19	1.46e+07	Alpha, Beta	208Tl (35.94%), 212Po (64.06%)
213	Bi	4.56e-01	m	2735.4	4.30e+19	1.94e+07	Alpha, Beta	209Tl (2.16%), 213Po (97.84%)
212	Po	2.98e-07	s	2.98e-07	3.96e+29	1.79e+17	Alpha	208Pb
213	Po	4.00e-06	s	0.000004	2.94e+28	1.32e+16	Alpha	209Pb
215	Po	1.78e-03	s	0.00178	6.54e+25	2.95e+13	Alpha	211Pb
216	Po	1.45e-01	s	0.145	9.00e+23	3.60e+11	Alpha	212Pb
217	At	3.20e-02	s	0.332	3.61e+24	1.62e+12	Alpha	213Bi
219	Rn	3.96e+00	s	3.96	2.39e+22	1.30e+10	Alpha	215Po
220	Rn	5.56e-01	s	55.6	2.35e+21	9.22e+08	Alpha	216Po
222	Rn	3.32e+00	d	330350.4	3.41e+21	1.54e+05	Alpha	218Po
221	Fr	4.80e+00	m	288	2.93e+20	1.77e+08	Alpha	217At
223	Fr	2.18e+01	m	1308	8.59e+19	3.87e+07	Beta	223Ra
223	Ra	1.14e+01	d	987984	1.14e+17	5.12e+04	Alpha	219Rn
224	Ra	3.56e+00	d	316224	3.54e+17	1.59e+05	Alpha	220Rn
225	Ra	1.49e+01	d	1287360	8.65e+16	3.89e+04	Beta	225Ac
226	Ra	1.60e+03	y	5.35e+10	2.19e+12	9.89e+01	Alpha	222Rn

WHC-SD-WM-TI-528, Rev. 1
TABLE 5-1 continued.

Radionuclide		Half-life (term)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	Ci/g		
228	Ra	5.76e+00	y	1.82e+08	6.04e+14	2.72e+02	Beta	228Ac
225	Ac	1.00e+01	d	864000	1.29e+17	5.80e+04	Alpha	221Fr
227	Ac	2.18e+01	y	6.87e+08	1.61e+14	7.23e+01	Beta,Alpha	227Th (98.62%), 223Fr (1.38%)
228	Ac	6.15e+00	h	22140	4.95e+18	2.23e+05	Beta	228Th
227	Th	1.87e+01	d	1617408	6.82e+16	3.07e+04	Alpha	223Ra
228	Th	1.91e+00	y	60368036	1.82e+15	8.20e+02	Alpha	224Ra
229	Th	7.30e+03	y	2.30e+11	4.75e+11	2.14e-01	Alpha	225Ra
230	Th	7.54e+04	y	2.38e+12	4.58e+10	2.06e-02	Alpha	226Ra
231	Th	1.06e+00	d	91843.2	1.18e+18	5.32e+05	Beta	231Pa
232	Th	1.40e+10	y	4.42e+17	2.44e+05	1.10e-07	Alpha	228Ra
234	Th	2.41e+01	d	2082240	5.14e+16	2.32e+04	Beta	234Pa
231	Pa	3.28e+04	y	1.03e+12	1.05e+11	4.72e-02	Alpha	227Ac
233	Pa	2.70e+01	d	2332800	4.61e+16	2.08e+04	Beta	233U
234	mPa	1.17e+00	m	70.2	1.52e+21	6.87e+08	Beta,IT	234U (99.87%), 234Pa (0.13%)
232	U	7.00e+01	y	2.21e+09	4.89e+13	2.20e+01	Alpha	228Th
233	U	1.59e+05	y	5.02e+12	2.14e+10	9.64e-03	Alpha	229Th
234	U	2.46e+05	y	7.76e+12	1.38e+10	6.21e-03	Alpha	230Th
235	U	7.04e+08	y	2.22e+16	4.80e+06	2.16e-06	Alpha	231Th
236	U	2.34e+07	y	7.39e+14	1.44e+08	6.47e-05	Alpha	232Th
238	U	4.47e+09	y	1.41e+17	1.46e+05	3.36e-07	Alpha	234Th
236	No	1.55e+05	y	4.89e+12	2.17e+10	9.77e-03	EC,Beta,Alpha	236U, 236Pu, 232Pa (91/8.9/0.1%)
237	No	2.14e+06	y	6.75e+13	1.56e+09	7.05e-04	Alpha	233Pa
239	No	2.36e+00	d	203472	5.15e+17	2.32e+05	Beta	239Pu
236	Pu	2.87e+00	y	90567832	1.17e+15	5.28e+02	Alpha	232U
238	Pu	8.77e+01	y	2.77e+09	3.30e+13	1.71e+01	Alpha	234U
239	Pu	2.41e+04	y	7.51e+11	1.38e+11	6.20e-02	Alpha	235U
240	Pu	6.56e+03	y	2.07e+11	5.34e+11	2.27e-01	Alpha	236U
241	Pu	1.44e+01	y	4.54e+08	2.79e+14	1.03e+02	Beta	241Am
242	Pu	3.75e+05	y	1.18e+13	3.13e+05	3.94e-03	Alpha	238U
244	Pu	8.00e+07	y	2.52e+15	4.37e+07	1.83e-05	Alpha,SPF	240U (99.35%), fission prod (0.65%)
241	Am	4.33e+02	y	1.37e+10	1.51e+12	3.43e+00	Alpha	237No
242	Am	1.60e+01	h	57672	1.79e+18	8.08e+05	Beta,EC	242Cm (82.7%), 242Pu (17.3%)
242	mAm	1.41e+02	y	4.45e+09	2.33e+13	1.05e+01	IT,Alpha	242Am (99.55%), 238No (0.45%)
243	Am	7.37e+03	y	2.33e+11	4.43e+11	2.00e-01	Alpha	239No
242	Cm	1.63e+02	d	14065920	7.36e+15	3.31e+03	Alpha	238Pu
243	Cm	2.91e+01	y	9.18e+08	1.12e+14	5.05e+01	Alpha,EC	239Pu (99.76%), 243Am (0.24%)

WHC-SD-WM-TI-528, Rev. 1
TABLE 5-1 continued.

Radionuclide		Half-life (years)		Half-life (seconds)	Specific Activity		Decay mode	Daughters (by decay mode)
					dpm/g	Ci/g		
244	Cm	1.81e+01	y	5.71e+08	1.80e+14	8.09e+01	Alpha	240Pu
245	Cm	8.50e+03	y	2.68e+11	3.81e+11	1.72e-01	Alpha	241Pu
246	Cm	4.76e+03	y	1.50e+11	6.78e+11	3.05e-01	Alpha	242Pu
247	Cm	1.56e+07	y	4.92e+14	2.06e+08	9.28e-05	Alpha	243Pu
248	Cm	3.48e+05	y	1.10e+13	9.19e+09	4.14e-03	Alpha,SPF	244Pu(91.74%),fiss.prod(8.26%)
252	Cf	2.64e+00	y	83246670	1.19e+15	5.38e+02	Alpha,SPF	248Cm(96.908%),fiss.prod(3.092%)

Westinghouse
Savannah River Company

P.O. Box 616
Aiken, SC 29802

SRT-WED-94-0077

April 26, 1994

Incoming 9401771

George F. Williamson
Manager, Low Level Waste Program; R4-01
Westinghouse Hanford Co.
P. O. Box 1970
Richland, Washington 99352

MAY 1 1994

STANDARD

REQUEST FOR ADDITIONAL INFORMATION FOR PRP REVIEW OF HANFORD
GROUT PA (U)

Dear George:

The DOE Peer Review Panel met in Salt Lake City on April 21 and 22, 1994 to complete the review of the revised Hanford Grout Performance Assessment (WHC-SD-WM-EE-004, Rev. 0, 10/93). The Panel had met on February 9 and 10, 1994 to begin the review. At the February meeting, the Panel requested some additional information to aid the review.

In the April review, the Panel concluded that more information is necessary to complete the review. The request for that information is stated below. During the meeting, the Panel noted the high quality of the revised Performance Assessment (PA). The Panel also noted the timely and complete response to our request for additional information at the February meeting. The response alleviated the concerns noted during that meeting.

During the April meeting, the Panel considered whether the PA could be approved. After much debate, the Panel decided that the PA, as issued, did not provide the basis to conclude, with reasonable assurance, that the analysis bounded the performance of the grout disposal facility. Thus, to enable the Panel to approve the PA, the information requested below is necessary.

I want to be sure that you understand that the Panel is very complimentary of the much improved quality and completeness of the PA. The Panel also commends the Westinghouse and Battelle staff for their thorough and complete response to our earlier request for information. The Panel had intended that our earlier request would provide enough information to conclude the review. However, because of the complexity of the PA, it became evident that the information noted below is necessary to ensure a bounding analysis.

RECEIVED

MAY 03 1994 R.153

G. F. WILLIAMSON

G. F. Williamson
SRT-WED-94-0077
April 26, 1994
page 2 of 3

The Panel has scheduled meetings on May 23 and 24, June 13 and 14, and June 30 and July 1 to begin the review of other Performance Assessments. The Panel will include the consideration of your response to our request and move to conclude the review of the Grout PA as soon as possible after you have provided the requested information. If possible, please provide the information before one of the scheduled meetings.

To expedite distribution of the information to the Panel, please express mail or telefax the information to the Panel's Technical Secretary, Mr. Robert U. Curl, EG&G Idaho. Dr. Charles Kincaid, who provided the earlier information, has Mr. Curl's address and fax number.

If you have any questions or if I can help further, please let me know.

Sincerely,

Elmer L. Wilhite, Chairman
DOE Peer Review Panel
Advisory Scientist
Savannah River Technology Center
803-725-5800

CC: Peer Review Panel Members and Advisors

J. A. Turi, EM-32	D. W. Nobles, EM-332
G. J. Duggan, EM-332	R. U. Curl, EG&G
K. W. Owens, SAIC	D. E. Wood, WHC
W. E. Stevens, 773-A	

REQUEST FOR ADDITIONAL INFORMATION ON THE
PERFORMANCE ASSESSMENT OF GROUTED DOUBLE-
SHELL TANK WASTE DISPOSAL AT HANFORD

Information Request

Provide the Panel information to allow the assessment of the dose impact for the Central Compliance case for the Groundwater Protection and Garden scenarios, as well as the Farm scenario, with failure of the asphalt barrier, concrete vault and grout at a time earlier than presented in the PA. A time on the order of hundreds of years after disposal is requested. Include information to show the impact of other radionuclides in addition to those presented in the PA (^{129}I , ^{99}Tc , ^{237}Np , and ^{126}Sn) or to conclude that no other radionuclides contribute significantly to dose, even with earlier barrier failure. Provide an interpretation of how this information relates to that presented in the PA.

G. F. Williamson
SRT-WED-94-0077
April 26, 1994
page 3 of 3

Rationale for Request

The information presented in the PA does not permit the assessment of dose impacts for earlier barrier failure. Figure 4.26 presents results of the various design cases, but only for the Farm scenario, and the figure does not clearly identify which radionuclides contribute significantly to the dose. Although the PA considers a wide range of failure mechanisms in formulating the Central Compliance and Central Sensitivity Cases, sulfate attack and calcium hydroxide leaching apparently were not incorporated into degradation modeling. In view of this, and the recent discussions within the commercial LLW disposal community regarding the lifetime of concrete disposal units (less than 500 years seems to be the consensus at present), the Panel requests consideration of failure of the Grout disposal vault in the time frame of hundreds of years after disposal. Because of the potential for coupling of failure of the Grout with the vault, failure of the Grout should be coincident with vault failure.

Regarding the asphalt barrier, it is not clear that cold joints resulting from construction of the barrier can be discounted (Appendix O, page O.14); additionally, the geotechnical integrity of the soil structure underlying the Grout disposal facility was not discussed, thus, the potential for settlement which may result in cracking of the asphalt barrier cannot be assessed. Therefore, cracking of the asphalt barrier earlier than presented in the PA is necessary to provide reasonable assurance that the impacts of grout disposal have been bounded.

The PA presents results of numerous sensitivity and design cases, but only for the Farm scenario. Inspection of Table 4.2 indicates that the Groundwater Protection and Garden Scenarios are more sensitive indicators of performance. In addition, results for less important transport groups were only presented for the Central Sensitivity Case (Figure 4.23). Thus, to ensure that the documentation provides sufficient information to conclude, with reasonable assurance, that the performance of the grout disposal facility has been bounded, the presentation of the information requested should include the dose impact for the Groundwater Protection and Garden scenarios, as well as the Farm scenario, for enough of the radionuclides to conclude that all significant radionuclides have been included.

Providing an interpretation of this information to put it into context with the information presented in the PA will aid the Panel's review of the information.

June 16, 1994

Mr. George F. Williamson
Westinghouse Hanford Operations
P.O. Box 1970
MSIN R4-01
Richland, WA 99352

Dear Mr. Williamson:

Ref: Letter from E. L. Wilhite to you dated April 26, 1994, requesting additional information to supplement the Hanford Grout Performance Assessment (PA); letter number SRT-WED-94-0077.

In response to the Peer Review Panel (PRP) request for additional information, Hanford staff have prepared the attached description of cases and results.

The request was for information regarding the dose impacts associated with early release brought about by an unanticipated failure of principle elements of the engineered system. These elements were identified in the request as the asphalt barrier, concrete vault, and grout waste form. The request specified significant failure and hence release should begin in the hundreds of years time frame. In addition, the PRP requested that the complete inventory be analyzed to ensure that all significant radionuclides were included in the analysis.

To respond as soon as possible, the Hanford staff selected two cases for further analysis. Flow and transport analyses for both cases were available from our original analyses in support of the grout performance assessment. The first case, Case A, involved a time-shift of the Central Compliance Case. By imposing a simple time-shift to the original solution, the first major degradation episode was imposed after only 500 years instead of 5000 years. The second case, Case B, in which the degradation was too severe to be credible, involves the assignment of backfill soil hydraulic properties to the asphalt-barrier, concrete-vault, and grout waste form elements of the engineered system.

Analyses of the cases reveal the potential dose impacts associated with the early onset of severe degradation of the engineered disposal system. Analysis of the complete inventory in the time-shifted Central Compliance Case revealed that no additional radionuclides, beyond those identified in the PA (October 1993 version), contribute significantly to peak dose estimates. The regulatory performance objectives (i.e., performance objectives during the 0 - 1000 year time-frame) were met in all three exposure scenarios for both cases. During the programmatic performance objective period (i.e., performance objectives during the 1000 - 10,000 year time-frame), the time-shifted Central Compliance Case violated the groundwater protection standard for the drinking water exposure scenario but met the all-pathways standard for the family farm and garden exposure scenarios. The non-credible case violated groundwater protection and all-pathways standards for all three exposure scenarios during the programmatic performance objective period.

Mr. George F. Williamson
 June 16, 1994
 Page 2

The attachment describes both cases, presents the new analyses, and provides a comparison of the new results to the results of the original Central Compliance Case presented in the PA.

The attachment was hand carried by W. E. Kennedy, Jr., to the June 13 - 14 PRP meeting in Charleston, South Carolina. It was subsequently distributed to the members of the PRP at that meeting. This provided the PRP an opportunity to briefly review the information packet and obtain clarification on any ambiguous text, prior to their final review and discussion of the Hanford Grout PA at the next PRP meeting. That meeting is now scheduled for June 30 - July 1 in San Francisco, California.

If you or your staff have questions regarding this submittal in response to the PRP request, please contact me at (509) 376-8324.

Very truly yours,

C. T. Kincaid, Staff Scientist
 Near Surface Hydrologic Processes Technical Group
 EARTH & ENVIRONMENTAL SCIENCES CENTER

CTK/tar

Attachment

cc:	K. C. Burgard	R4-01
	J. M. Conner	L4-75
	R. U. Curl	EG&G Idaho
	D. W. Hendrickson	L5-31
	R. A. Karnesky	H0-40
	F. M. Mann	H0-36
	C. A. Oster	L4-91
	M. G. Piepho	H0-36
	J. A. Rawlins	H0-36
	J. W. Shade	L4-75
	J. A. Voogd	R4-01
	D. E. Wood	H0-33
	M. I. Wood	N3-13

RESPONSE TO THE SECOND PRP INFORMATION REQUEST

10 June 1994

Subject: Hanford Site response to the second request for additional information for PRP review of the Hanford Grout Performance Assessment. The document being reviewed is referenced as follows:

Kincaid, C.T., J.W. Shade, G.A. Whyatt, M.G. Piepho, K. Rhoads, J.A. Voogd, J.H. Westsik, Jr., M.D. Freshley, K.A. Blanchard, B.G. Lauzon. October 1993. Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford, Volumes 1 and 2. WHC-SD-WM-EE-004, Rev.0. Westinghouse Hanford Company, Richland, Washington.

The information requested was described in letter number SRT-WED-94-0077 dated April 26, 1994 from Elmer L. Wilhite, Chairman of the DOE Peer Review Panel, to George F. Williamson, Manager of the Low-Level Waste Program at Westinghouse Hanford Company. The information request reads as follows:

"Provide the Panel information to allow the assessment of the dose impact for the Central Compliance case for the Groundwater Protection and Garden scenarios, as well as the Farm scenario, with failure of the asphalt barrier, concrete vault and grout at a time earlier than presented in the PA. A time on the order of hundreds of years after disposal is requested. Include information to show the impact of other radionuclides in addition to those presented in the PA (^{129}I , ^{99}Tc , ^{237}Np , and ^{126}Sn) or to conclude that no other radionuclides contribute significantly to dose, even with earlier barrier failure. Provide an interpretation of how this information relates to that presented in the PA."

In response to the request, Hanford Site personnel have selected two cases which will exhibit aspects of early release resulting from a lack of integrity within the asphalt, concrete and grout engineered components. The first case (Case A) is the Central Compliance (CC) case with a time shift of 4500 years and with doses calculated for an expanded list of radionuclides. The second case (Case B) is a "non-credible" case in which the hydraulic properties of the asphalt barrier, concrete vault, and grout are assigned the properties of backfill soil for all time.

CASE A: THE TIME-SHIFTED CENTRAL COMPLIANCE (CC) CASE

To achieve the time shift in the central compliance (CC) case, 4500 years was subtracted from the time values in the dimensionless concentration vs. time results for each transport group. This time-shift is accomplished prior to application of radioactive decay calculations so that radioactive decay does not begin until time=0 (4500 years in the initial simulation). The

result is an approximation of the results that might be obtained if the significant degradation beginning at 5000 years were to occur instead at 500 years.

Results for drinking water were calculated for all radionuclides by calculating transport group 2B as if it were group 2A and calculating group 4D both as if it were group 3C and as if it were 4A. This is the equivalent of ignoring or under-representing sorption in the soil and grout which will over state the impact of these radionuclides. All radionuclides which were not previously calculated for the farm and garden scenarios and contributed at least 0.005 mrem/yr or 0.1% of the total dose to the drinking water dose were included in the farm and garden scenario dose calculations.

The Time Shift

The decision to time-shift the CC case was made knowing the approach is not technically rigorous, but with an interest in providing a reasonable response in a timely manner. The original CC case included moderate degradation which allowed only limited release prior to 5000 years. After 100 years, 5-mm corner cracks were assigned to the upper corner regions of the asphalt. These cracks enabled infiltrating waters to contact the concrete. However, with the exception of the roof plank joint cracks and construction joint cracks the remainder of the barrier and concrete were modelled as being intact until approximately 5000 years. The more severe general degradation (and the beginning of significant releases from the vault) was begun with the asphalt barrier being degraded by the introduction of 1-mm cracks every meter at 5000 years and the concrete vault was degraded by the introduction of 1-mm cracks every meter at 5150 years.

In the CC case, very little of the inventory was released from the engineered disposal system over the first 4500 years, and even less was transported out of the vadose zone profile. The percentage of the original inventory in each transport group that was lost from the vadose zone during the first 4500 years in the CC case has been calculated and is reported below.

<u>Transport Group</u>	<u>Cumulative Percentage (%) of Inventory Released to Aquifer in < 4500 yr</u>
1A	1.23×10^{-2}
2A	1.25×10^{-3}
2B (modeled as 2A)	1.25×10^{-3}
3A (not modeled) ¹	
3C ²	0
4A	2.59×10^{-7}
4D (modeled as 4A)	2.59×10^{-7}
4D (modeled as 3C)	0

¹ no radionuclides modeled in this transport group

² contaminant has not yet arrived at the water table

Clearly, the inventory released prior to 4500 years is not significant. In addition, the peak in the dose curves in response to the degradation assigned at 5000 years was two orders of magnitude greater than doses predicted prior to 5000 years. Thus, neglecting the inventory released to the aquifer over the first 4500 years should not be significant.

Reasonable application of the time shift is limited to the 5000 year time period prior to significant release from the engineered system. Application to times after significant release from the engineered system would result in a qualitatively different response due to the loss of radionuclides and the significantly altered initial distribution of contaminants.

As a result of the application of the time shift, the low-level release of some mobile contaminants occurs immediately. This is because at the new initial time there is some contaminant in the soil profile which does not experience the approximately 2000 year travel time from the engineered system to the aquifer. Using the time-shift model suggests an unrealistic release during the first 1000 years; a time period during which nothing would actually reach the water table. Furthermore, the time-shifted model may influence the early estimates of dose associated with releases from the degraded upper corners of the asphalt barrier. However, the release associated with the more substantial degradation assigned to occur after 500 years should not be significantly influenced.

SELECTION OF 500 YEARS FOR THE ONSET OF SIGNIFICANT DEGRADATION

The basis for translating the degradation occurring after 5,000 years to 500 years is as follows:

- i) The 500 years is a relative value, selected to be midway through the "hundreds of years" period requested, and

roughly related to the timing of degradation in the NRC branch technical position paper.

ii) Significant degradation of the asphalt barrier, concrete and grout begins at 5000 years. Thus, to be responsive to the request, this time period needs to be shifted to a time in the hundreds of years.

iii) Time shifting from times greater than 5000 years would not produce reasonable results. The release from the engineered system occurring after 5000 years would cause the result of a time shift from a time greater than 5000 years to be a poor representation of the expected result.

Thus, the 4500 year time shift provides significant degradation within the requested time frame of the PRP while providing a reasonable approximation to the expected performance. It should be noted that professional judgement indicates the magnitude of degradation, as indicated by substantial through-wall cracks, associated with 500 years in the time shifted case is not expected to occur until sometime during the 10,000 to 100,000 year time frame.

CASE B: THE NON-CREDIBLE, DEGRADED-TO-SOIL CASE

This case was originally simulated to demonstrate the benefit of different features of the engineered system in limiting release. It was calculated in the same spirit as the design cases presented in the PA document but was not included in the PA document. In this simulation, the asphalt barrier, concrete, and grout are assigned the hydraulic properties of backfill soil. Only the RCRA barrier and the gravel layer which are composed of natural earthen materials retained normal hydraulic properties in this analysis. The sorption properties within the grout were maintained and the sorption properties of backfill soil were assigned to the concrete and asphalt barrier regions. This case might be used to represent an incredible and complete degradation of hydraulic properties of the grout, concrete and asphalt barrier.

Unlike the CC case which represents stages of degradation by periodically changing material properties and restarting the simulation, this case was simulated as a single suite of material properties assigned initially and unchanged throughout time. The degradation represented by soil hydraulic properties being assigned to the waste form and key engineered barriers is simulated from time zero, and is not time-shifted as was done in the time-shifted CC case analysis. Although the material properties are assigned from the start of the simulation the doses do not become significant until after 2000 years due to the travel time required to traverse the vadose zone.

Under no circumstances is this level of degradation for the

grout waste form, concrete vault, or asphalt barrier foreseeable in the hundreds of years time frame. Accordingly, this analysis is not credible. However, it is felt that this analysis will certainly bound any estimate of impact due to early degradation.

THE EXPOSURE & DOSE ANALYSIS

Three exposure scenarios are analyzed for both the time-shifted CC case and the non-credible degradation-to-soil case; groundwater protection (drinking water), family garden, and family farm. In both of these cases the analysis begins with a full inventory analysis of the drinking water scenario. In the case of the time-shifted central compliance case, the inventory list analyzed includes radionuclides in transport groups 2B and 4D by adding them to more conservative transport groups. In the case of the non-credible, degraded to soil case, the list of radionuclides does not include the transport groupings 2B and 4D based on the results obtained in the time-shifted central compliance case. Subsequently, those radioactive isotopes contributing 0.1% or more to the drinking water dose are analyzed for contribution to the family garden and family farm dose. The rationale for analyzing a short list of isotopes for the latter two scenarios is based on the observation that ingestion constitutes the largest share of the dose for these scenarios, although other exposure pathways are included. Dose from drinking water, which adequately characterizes the ingestion pathway, was used as the screening tool to determine the relative contribution of radionuclides. External exposure to radionuclides deposited on the ground is only a significant exposure pathway for a few radionuclides such as Co-60, Nb-94, Cs-137, and Sn-126, which are either included in the dose calculations or are sufficiently short-lived that they are not a concern in the groundwater transport scenarios. Therefore, this screening procedure is unlikely to result in omission of radionuclides that could contribute significantly to the total dose, and it is estimated that the radionuclides evaluated account for greater than 99% of the total dose.

RESULTS AND DISCUSSION

Results are presented first for the central compliance case in the performance assessment document to provide a point of comparison. Results are then presented for the time-shifted central compliance case (Case A) and then for the non-credible degraded to soil case (Case B).

Central Compliance Case

The results in the form of fractional release to the aquifer/yr are presented in Figure 1. The curves in this figure represent the transport groupings 1A, 2A, 3C and 4A. The radionuclides in transport groupings 2B and 4D were neglected in the central compliance case.

Figure 2 shows the central compliance case drinking water doses that were obtained in the performance assessment. Figures 3 and 4 provide the results from the performance assessment document for the irrigated garden and farm scenarios respectively.

Case A: Time-Shifted Central Compliance Case

The results for the time-shifted central compliance case in the form of fractional release to the aquifer/yr are presented in Figure 5. The curves in this figure represent the transport groupings 1A, 2A, 3C and 4A. In the time-shifted case, radionuclides in transport group 2B (Nb-94, Nb-95) were calculated as group 1A. Radionuclides in group 4D were calculated both as group 4A and as group 3C to check for significance. The radionuclides included from group 4D included Am-241, CePr-144, Cm-243, Cm-244, Eu-152, Eu-154, Eu-155, Pu-238, Pu-239/240, Pu-241, Pu-242, Th-230, Zr-95.

Figure 6 shows the time-shifted central compliance case drinking water doses. For the drinking water scenario, all radionuclides in all of the transport groupings were included in the calculation. Figures 7 and 8 provide the results for the irrigated garden and farm scenarios respectively.

For the calculation of radionuclides in the irrigated garden and farm scenarios, any radionuclide contributing 0.005 mrem/yr¹ to the drinking water dose and which was not already included in the calculation was added to the list of radionuclides analyzed. All of the radionuclides from group 2B and 4D were negligible (<0.005 mrem/yr) with the exception of Pu-239/240 which contributed a maximum of 1.24 mrem/yr to drinking water and 1.00

¹ The actual screen used was 0.1% of the total dose. However, no radionuclide removed with this screen contributes more than 0.005 mrem/yr.

mrem/yr to the garden scenario when calculated in group 3C. The peak dose using group 4A transport properties was lower (0.72 mrem/yr drinking water, 0.582 mrem/yr garden). For purposes of plotting, the higher dose resulting from use of transport group 3C properties was used. The impact of Pu-239/240 would be substantially reduced because of the significant retardation in the soil expected (group 4D soil $R_d=21$ ml/g vs group 3C soil $R_d=3$ ml/g) is not taken into account. However, the impact of transport groups 2B and 4D is bounded by this approach.

The fractional release results for the time-shifted case indicates low levels of arrival occurring for transport groups 1A and 2A from the start of the simulation. This is due to the material existing in the soil column at the beginning of the simulation. This is an artifact of the time shift and in reality these radionuclides would not begin arriving until after an approximate 2000-year travel time.

The time-shifted results for the drinking water scenario begin violating the 4 mrem /10,000 year programmatic performance objective after about 5250 years and reaches a dose of 7.7 mrem/yr at 10,000 years. The magnitude of the maximum peak is the same as the compliance case (18.7 mrem/yr). In the farm and garden scenarios the results are shifted in a similar manner. The 25 mrem, 10,000 year programmatic performance objective is still met despite the time shift.

In comparing the results from the time-shifted compliance case to the compliance case it was observed that the short-lived radionuclides Sb-125 and RuRh-106 showed up in the first few years as significant. However, this is an artifact of the time shift. Because some amount of these radionuclides are reaching the accessible environment at the new time zero, they do not have an opportunity for radioactive decay during transport. In reality these radionuclides would decay to negligible levels before reaching the accessible environment. These radionuclides do not show up on the dose plots because they decay to negligible levels prior to 100 years which marks the left axis of the logarithmic plot.

Case B: The Non-Credible Degradation to Soil Case

In this case the asphalt barrier, concrete vault, and grout are assigned the hydraulic properties of backfill soil from the start of the simulation. The fractional release results are shown in figure 9. Simulation results for this case are only available through 24,800 years which is sufficient to see the major peak formed by iodine-129 and technetium-99. Multiple peaks resulting from the mobile radionuclides are not expected in this case because the properties of the system are not being degraded in steps over time as they were in the compliance cases. Transport group 3C has not arrived at the aquifer at the time this case was terminated. A second peak caused by Np-237 would

be expected after 30,000 years. Because the group 2B transport group was shown to be negligible and group 4D can be modeled as group 3C which hasn't yet arrived, this case was calculated using the same radionuclides as in the original central compliance case.

The results for this case are shown in Figures 10, 11, and 12 for the drinking water, garden and farm scenarios respectively. In each scenario, the regulatory performance objective is met at 1000 years due to the travel time required to reach the accessible environment. The 4 mrem/yr programmatic performance objective for drinking water dose (Figure 10) is exceeded at approximately 3800 years and peaks at 7400 years at a dose of 125 mrem/yr. While this dose is considerably above the programmatic performance objective it is not a catastrophic event. The garden and farm results are qualitatively similar to the drinking water result except that the dose limit is higher (25 vs 4 mrem/yr) and is violated later (4500 yr garden, 4600 yr farm). The dose contribution from U-234 for the farm scenario is just below 0.1 mrem/yr and therefore does not appear in the farm scenario plot (Figure 12).

CONCLUSIONS

The time-shifted compliance case (Case A) demonstrates that early onset of severe degradation of the engineered system would result in violation of the programmatic performance objective for groundwater protection (4 mrem/yr). However, performance objectives for the farm and garden scenarios are still met. The inclusion of all radionuclides for dose calculations by assigning more conservative transport properties to radionuclides in transport groupings 2B and 4D confirmed that these radionuclides were not significant contributors to dose.

The non-credible degradation to soil case (Case B) indicates that extreme degradation of the hydraulic properties of the grout, concrete, and asphalt barrier immediately after disposal would result in the violation of the programmatic performance objectives in each of the three scenarios. However, the doses projected are not catastrophic. There is no credible scenario that could result in the extent of degradation considered in this case. However, the results of this case bound the impact of degradation in the hydraulic properties of the grout, concrete vault and asphalt barrier.

In both of the cases examined, the regulatory performance objectives at 1000 years were met for all exposure scenarios.

8/25

Figure 1 Fractional Release to the Groundwater Per Year for the Central Compliance Case. Effects of radioactive decay are not included. Curves correspond to results for transport groupings: iodine-129, group 1A; technetium-99, group 2A; neptunium -237, group 3C; uranium-238, group 4A.

9/25

Figure 2 Central Compliance Case Drinking Water Doses. Curves remaining outside shaded regions indicate performance objectives are met.

10/25

Figure 3 Central Compliance Case Irrigated Garden Scenario Doses. Curves remaining outside shaded regions indicate performance objectives are met.

11/25

Figure 4 Central Compliance Case Irrigated Farm Scenario Doses. Curves remaining outside shaded regions indicate performance objectives are met.

12/25

Figure 5 Fractional Release to the Groundwater Per Year for the Time-Shifted Central Compliance Case (Case A). Effects of radioactive decay are not included. Curves correspond to results for transport groupings: iodine-129, group 1A; technetium-99, group 2A; neptunium -237, group 3C; uranium-238, group 4A. Radionuclides in transport group 2b are included in 1A. Radionuclides in group 4D are modelled in 3C (Pu-239/240).

Figure 6 Time-Shifted Central Compliance Case (Case A) Drinking Water Doses. Curves entering shaded regions indicate where performance objectives are not met.

14/25

Figure 7 Time-Shifted Central Compliance Case (Case A) Irrigated Garden Scenario Doses. Curves remaining outside shaded regions indicate performance objectives are met.

15/25

Figure 8 Time-Shifted Central Compliance Case (Case A) Irrigated Farm Scenario Doses. Curves remaining outside shaded regions indicate performance objectives are met.

16/25

Figure 9 Fractional Release to the Groundwater Per Year for the Non-Credible Degradation to Soil Case (Case B). Effects of radioactive decay are not included. Curves correspond to results for transport groupings: iodine-129, group 1A; technetium-99, group 2A; neptunium-237, group 3C; uranium-238, group 4A.

17/25

Figure 10 Non-Credible Degradation to Soil Case (Case B) Drinking Water Doses. Curves entering shaded regions indicate where performance objectives would not be met.

18/25

Figure 11 Non-Credible Degradation to Soil Case (Case B)
Irrigated Garden Scenario Doses. Curves entering
shaded regions indicate where performance objectives
would not be met.

19/25

Figure 12 Non-Credible Degradation to Soil Case (Case B)
Irrigated Farm Scenario Doses. Curves entering shaded
regions indicate where performance objectives would not
be met.

20/25

Supplementary Information

1. The transport groups and the associated radionuclides are provided. In the time-shifted central compliance case all of these radionuclides were simulated for the drinking water scenario. After a 0.1% screen on the drinking water dose the remainder were calculated for the farm and garden scenarios. Species shown in group 4D were calculated as if transport properties matched group 3C and group 4A. The maximum doses obtained are shown later in this section. In the "non-credible degraded to soil" case, the nuclides shown in group 2B and 4D were neglected based on results obtained in the time-shifted central compliance case.
2. Results obtained for radionuclides in group 4D modelled as group 4A or 3C are shown for the time-shifted central compliance case. The largest contribution is obtained from Pu239/240 modelled as group 3C.
3. The radionuclides included in the drinking water calculation for the time-shifted central compliance case are shown. The maximum dose contributed at any time is shown for the drinking water scenario and the irrigated garden scenario. Values crossed out indicate that the calculation was not performed for that radionuclide in the irrigated farm and garden scenarios.
4. The dose factors for the farm and garden scenarios are shown for the radionuclides considered in the calculations for the time-shifted central compliance case. Missing values in the irrigated farm and garden scenario columns indicate these radionuclides were neglected in these scenarios. The decision to neglect radionuclides was made based on the drinking water dose which was calculated.

21/25

Table 3.15. Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments

Transport Group	Species	Grout $R_d^{(a)}$ (ml/g)	Soil $R_d^{(b)}$ (ml/g)
1A	^3H , ^{103}Ru , $^{106}\text{RuRh}$, ^{125}Sb , ^{129}I	0	0
2A	^{99}Tc	2	0
2B	^{94}Nb , ^{95}Nb	2	0.67
3A	Selected chemicals only	125	0
3C	^{60}Co , ^{63}Ni , ^{79}Se , ^{90}Sr , ^{113}Sn , ^{126}Sn , ^{134}Cs , ^{135}Cs , ^{137}Cs , ^{226}Ra , ^{237}Np	125	3
4A	^{14}C , ^{234}U , ^{235}U , ^{238}U	2.625	0
4D	^{95}Zr , $^{144}\text{CePr}$, ^{152}Eu , ^{154}Eu , ^{155}Eu , ^{230}Th , ^{238}Pu , ^{239}Pu , ^{240}Pu , ^{241}Pu , ^{242}Pu , ^{241}Am , ^{243}Cm , ^{244}Cm	2.625	21

- (a) The retardation factor, R , is calculated from the distribution coefficient, R_d . The relationship is $R = 1 + (\rho_b R_d / \theta)$. For grout the additional data are as follows: particle density = 2.62 g/ml, $\theta = 0.5781$, bulk density = particle density $\times (1 - \theta)$.
- (b) The additional data for soils are as follows: All particle densities, $\rho_b = 2.72$ g/ml; backfill soil, $\theta = 0.371$; Hanford formation sandy sequence, $\theta = 0.4203$; Hanford formation gravel sequence, $\theta = 0.3584$; Ringold formation, $\theta = 0.4982$.

/.

22/25

		Max's for 4D as 4A		Max's for 4D as 3C	
		DW	IHG	DW	IHG
	Am241	3.80E-03	2.99E-03	7.17E-19	5.65E-19
	CePr144	3.60E-04	0.00E+00	0.00E+00	0.00E+00
ial (mre	Cm243	4.17E-06	0.00E+00	0.00E+00	0.00E+00
	Cm244	4.22E-06	0.00E+00	0.00E+00	0.00E+00
	Eu152	8.30E-07	0.00E+00	0.00E+00	0.00E+00
	Eu154	4.38E-05	0.00E+00	0.00E+00	0.00E+00
	Eu155	6.47E-06	0.00E+00	0.00E+00	0.00E+00
	Pu238	2.18E-05	0.00E+00	0.00E+00	0.00E+00
	Pu239/240	7.21E-01	5.82E-01	1.24E+00	1.00E+00
	Pu241	2.60E-05	0.00E+00	0.00E+00	0.00E+00
	Pu242	1.53E-05	0.00E+00	2.35E-04	0.00E+00
	Th230	2.12E-04	0.00E+00	1.59E-03	0.00E+00
	Zr95	1.21E-06	0.00E+00	0.00E+00	0.00E+00

DW = drinking water

IHG = irrigated home garden

2.

23/25

Nuclide	Peak GWater Concen. Ci/L	----All Times----	
		Drinking Water Dose	Irrigated Garden Dose
H-3	1.08E-11	4.99E-04	0.00E-00
C-14	3.21E-14	4.82E-05	5.46E-05
Co-60	0.00E+00	0.00E+00	0.00E+00
Ni-63	0.00E+00	0.00E+00	0.00E-00
Se-79	4.19E-12	2.55E-02	2.47E-02
Sr-90	0.00E+00	0.00E+00	0.00E+00
Nb-94	6.55E-14	2.42E-04	1.31E-03
Nb-95	2.66E-12	4.25E-03	0.00E-00
Tc-99	1.06E-08	1.01E+01	1.80E+01
Ru-103	6.47E-14	1.29E-04	0.00E-00
Ru/Rh-106	1.74E-09	2.61E+01	3.65E+01
Sn-113	0.00E+00	0.00E+00	0.00E-00
Sn-126	2.12E-11	2.54E-01	7.21E-01
Sb-125	8.96E-10	1.70E+00	5.47E+00
I-129	4.33E-11	8.66E+00	7.80E+00
Cs-135	4.54E-12	2.36E-02	2.22E-02
Cs-137	0.00E+00	0.00E+00	0.00E+00
Eu-152	1.89E-16	8.30E-07	0.00E-00
Eu-154	6.63E-15	4.38E-05	0.00E-00
Eu-155	6.82E-15	6.47E-06	0.00E-00
Ra-226	5.07E-27	4.05E-15	0.00E-00
Th-230	5.42E-16	2.12E-04	0.00E-00
U-234	1.04E-13	1.98E-02	2.09E-02
U-235	7.07E-15	1.27E-03	1.34E-03
U-238	2.87E-14	4.88E-03	5.17E-03
Np-237	2.88E-12	8.07E+00	1.07E+01
Pu-238	7.79E-18	2.18E-05	0.00E-00
Pu-239/40	4.01E-13	1.24E+00	1.00E+00
Am-241	1.15E-15	3.80E-03	2.99E-03
Cm-243	1.99E-18	4.17E-06	0.00E-00
Cm-244	2.48E-18	4.22E-06	0.00E-00
Pu-241	4.13E-16	2.60E-05	0.00E-00
Pu-242	5.11E-18	2.35E-04	0.00E-00
Zr-95	4.83E-16	1.21E-06	0.00E-00
Ce/Pr-144	2.40E-14	3.60E-04	0.00E-00
Total		2.79E+01	4.21E+01

Dose in mrem/yr

↑ "Total" reports peak value of the total dose curve.

Peak values of all radionuclides do not superimpose
at the same time.

3.

24/25

Pathway Dose Factors for Grout PA			
Nuclide	Drinking	Irrig.	Irrig.
	Water	Garden	Farm
	mrem/y	mrem/y	mrem/y
	per Ci/L	per Ci/L	per Ci/L
H-3	4.60E+07		
C-14	1.50E+09	1.70E+09	3.10E+09
Co-60	1.90E+10	4.10E+10	5.30E+10
Ni-63	3.90E+08		
Se-79	6.10E+09	5.90E+09	9.60E+09
Sr-90	9.50E+10	8.90E+10	9.50E+10
Nb-94	3.70E+09	2.00E+10	6.30E+10
Nb-95	1.60E+09		
Tc-99	9.50E+08	1.70E+09	4.30E+09
Ru-103	2.00E+09		
Ru/Rh-106	1.50E+10	2.10E+10	2.20E+10
Sn-113	2.00E+09		
Sn-126	1.20E+10	3.40E+10	6.70E+10
Sb-125	1.90E+09	6.10E+09	6.20E+09
I-129	2.00E+11	1.80E+11	2.90E+11
Cs-135	5.20E+09	4.90E+09	9.30E+09
Cs-137	3.70E+10	4.00E+10	7.00E+10
Eu-152	4.40E+09		
Eu-154	6.60E+09		
Eu-155	9.50E+08		
Ra-226	8.00E+11		
Th-230	3.90E+11		
U-234	1.90E+11	2.00E+11	2.10E+11
U-235	1.80E+11	1.90E+11	1.90E+11
U-238	1.70E+11	1.80E+11	1.90E+11
Np-237	2.80E+12	3.70E+12	3.70E+12
Pu-238	2.80E+12		
Pu-239/243	3.10E+12	2.50E+12	2.60E+12
Am-241	3.30E+12	2.60E+12	2.50E+12
Cm-243	2.10E+12		
Cm-244	1.70E+12		
Ce/Pr-144	1.50E+10		
Pu-241	6.30E+10		
Pu-242	3.00E+12		
Zr-95	2.50E+09		

4.

25/25

Battelle

Pacific Northwest Laboratories
 Battelle Boulevard
 P.O. Box 999
 Richland, Washington 99112
 Telephone (509) 376-8324

July 14, 1994

Dr. Elmer L. Wilhite
 % Mr. Robert U. Curl
 EG&G Idaho (TSB/M-8)
 765 Lindsay Blvd
 Idaho Falls, Idaho 83415-2420

Dear Elmer:

Ref: Response to requested clarification regarding Ru/Rh-106 doses shown in information dated 10 June 1994

Please find attached a brief explanation of the dose estimates for Ru/Rh-106. We had noted the elevated dose estimates for radioisotopes having short half lives and attempted to explain them in the original packet dated 10 June. I've called your attention to the relevant paragraphs and provided an interpretation specific to Ru/Rh-106.

If additional clarification is necessary on this or other points, please call me on (509) 376-8324, or FAX requests to me at (509) 376-5368.

Sincerely yours,

C. T. Kincaid, Staff Scientist
 Near Surface Hydrologic Processes Technical Group
 EARTH & ENVIRONMENTAL SCIENCES CENTER

CTK/tar

Attachment

cc:	K. C. Burgard	R4-01
	J. M. Conner	L4-75
	D. W. Hendrickson	L5-31
	R. A. Karnesky	H0-40
	F. M. Mann	H0-36
	C. A. Oster	L4-91
	M. G. Piepho	H0-36
	J. A. Rawlins	H0-36
	J. W. Shade	L4-75
	J. A. Voogd	R4-01
	G. F. Williamson	R4-01
	D. E. Wood	H0-33
	M. I. Wood	N3-13

**Re: Third page of supplementary information, page 24 of 25 in
RESPONSE TO THE SECOND PRP INFORMATION REQUEST dated 10 June 1994**

Requested Clarification:

Entries shown for maximum drinking water dose (column 3) and maximum irrigated garden dose (column 4) associated with the forecast peak groundwater concentration of Ru/Rh-106 are higher than expected. The PRP viewpoint is based on the observation that Ru/Rh-106 is assigned a half-life of 1.020 years and travel time through the vadose zone is long enough to require a sufficient number of half-lives to reduce Ru/Rh-106 to insignificant levels in the vadose zone and groundwater.

Clarification by the Hanford Grout PA Staff:

The third page of supplementary information included as part of our response is a list of peak groundwater concentrations and associated doses calculated as part of the time-shifted central compliance case. The PRP has noted a situation that arises because of our use of a time-shift to translate significant degradation that occurs at 5000 yrs in the Central Compliance Case to 500 yrs in the time-shifted analysis. We attempted to explain this behavior in our original supplemental information;

from page 3 of 25, 2nd full paragraph:

"As a result of the application of the time shift, the low-level release of some mobile contaminants occurs immediately. This is because at the new initial time there is some contaminant in the soil profile which does not experience the approximately 2000-year travel time from the engineered system to the aquifer. Using the time-shift model suggests an unrealistic release during the first 1000 years; a time period during which nothing would actually reach the water table. Furthermore, the time-shifted model may influence the early estimates of dose associated with releases from the degraded upper corners of the asphalt barrier. However, the release associated with the more substantial degradation assigned to occur after 500 years should not be significantly influenced."

from page 7 of 25, 1st full paragraph:

"The fractional release results for the time-shifted case indicates low levels of arrival occurring for transport groups 1A and 2A from the start of the simulation. This is due to the material existing in the soil column at the

beginning of the simulation. This is an artifact of the time shift and in reality these radionuclides would not begin arriving until after an approximate 2000-year travel time."

from page 7 of 25, 3rd full paragraph:

"In comparing the results from the time-shifted compliance case to the compliance case it was observed that the short-lived radionuclides Sb-125 and Ru/Rh-106 showed up in the first few years as significant. However, this is an artifact of the time shift. Because some amount of these radionuclides are reaching the accessible environment at the new time zero, they do not have an opportunity for radioactive decay during transport. In reality these radionuclides would decay to negligible levels before reaching the accessible environment. These radionuclides do not show up on the dose plots because they decay to negligible levels prior to 100 years which marks the left axis of the logarithmic plot."

To fully understand why non-zero Ru/Rh-106 concentrations appear, one must begin with the original Central Compliance Case. This case involves cracks in the upper corners of the asphalt barrier at early times. It also involves cracks in roof and other construction joints of the concrete vault from early times. As a result, releases begin from the engineered disposal system, albeit at minimal levels, at early times. The transport of radionuclides through the vadose zone is modeled in transport groups. Each group contains several radionuclides; each with its own decay half life. The elapsed time of the simulation, (e.g., at the groundwater well or other point of exposure), is used to calculate decay. Consequently, the intermediate result provided by the PORFLOW code includes non-zero Ru/Rh-106 concentrations in the aquifer because decay has not yet been applied. In the original Central Compliance Case, concentrations of Ru/Rh-106 leaving the vadose zone at the start of the simulation are zero. When finite values appear at later times, sufficient time has elapsed to enable decay to reduce the concentration to insignificant values.

In the time-shifted analysis, non-zero concentrations are leaving the vadose zone at time zero. This is a direct result of time-shifting non-decayed radionuclide concentrations from the PORFLOW output file. This, in turn, is a direct result of the calculation sequence adopted for the Hanford Grout PA, e.g., applying decay to the radionuclide concentration at the groundwater well. At early times in the time-shifted analysis, insufficient time has elapsed to allow decay to reduce Ru/Rh-106 concentrations to insignificant levels.

In reality, if the timing of degradation assumed to occur in the time-shifted case were simulated in a real-time sequence, (i.e., if we had simulated an entirely new case with the time sequence indicated and not used a time-shift to approximate the behavior), one would again see zero concentrations leaving the vadose zone initially. By the time any Ru/Rh-106 could leave the vadose zone, sufficient time would elapse to cause Ru/Rh-106 concentrations in the aquifer to be insignificant after decay was applied. Thus, the peak concentrations and doses shown for Ru/Rh-106 are not real. As our original statements indicated, this is an artifact of the time shift.

c:\wpwin\ctktxt\grout\prpjul94.ctl

PRP Requested Clarification

14 July 1994; Page 3 of 3

Battelle

Pacific Northwest Laboratories
Battelle Boulevard
P.O. Box 999
Richland, Washington 99352
Telephone (509)

376-8324

September 29, 1994

Mr. George F. Williamson
Westinghouse Hanford Operations
P.O. Box 1970
MSIN R4-01
Richland, Washington 99352

Dear Mr. Williamson:

On Tuesday, September 20, Mr. Stanley Neuder, a member of the Department of Energy Peer Review Panel (PRP), called with two questions on the Hanford Grout Performance Assessment (PA). Elmer Wilhite, chairman of the PRP, had assigned these issues to him for resolution.

After answering his questions, he asked if I would provide him a written summary of my responses. I agreed to do so. After having Bill Kennedy (PNL) and John Shade (WHC) review and comment on my draft, I forwarded the written response to Mr. Neuder on Friday, September 23.

A copy of the three page transmittal to Mr. Neuder is attached for your information.

Sincerely yours,

Charles T. Kincaid, Staff Scientist
Near Surface Hydrologic Processes Technical Group
EARTH AND ENVIRONMENTAL SCIENCES CENTER

CTK/tar

Attachment

cc: K. C. Burgard	R4-01
J. M. Conner	L4-75
D. W. Hendrickson	L5-31
F. M. Mann	HO-36
M. G. Piepho	HO-36
J. A. Rawlins	HO-36
J. W. Shade	L4-75
J. A. Voogd	R4-01
D. E. Wood	HO-33
M. I. Wood	N3-13

R.187

Responses to questions posed by Stan Neuder, PRP member, Battelle Washington Office, September 23, 1994.

QUESTION 1. Re: the supplemental results presented on the effects from an earlier breakdown of the barrier system [the central compliance case (CCC) versus the time-shifted central compliance case (TSCCC)]

Aside from the time shift, the results of the CCC and the TSCCC appear identical. Why? Shouldn't depletion of radionuclide inventory in the early period of the TSCCC release cause the later release, concentration, and dose to be somewhat lower than in the CCC?

RESPONSE 1. To be responsive to the PRP request (letter from E.L. Wilhite to G.F. Williamson dated April 26, 1994) to analyze for early barrier degradation we decided to perform a simple time shift of the CCC. In this approximation the time shift placed PORFLOW model results from the 4500 year time plane of the CCC at time zero of the TSCCC. The PORFLOW results are non-decayed contaminant flux from the vadose zone entering the groundwater aquifer. Decay is applied to each radionuclide in the inventory when groundwater well concentrations (or flux to the river) is calculated. Thus, when decay was applied in the TSCCC, it was over a period of time shortened by 4500 years from the CCC. Because of this, the resulting time-shifted analysis should yield slightly higher concentrations and doses.

The impact of the time-shift and decay calculation on our analysis for radionuclides with very short half-life (e.g. Ru-106) was described in our clarification to Dr. Wilhite (letter from C.T. Kincaid to E.L. Wilhite dated July 14, 1994). Radionuclides with intermediate half lives are expected to appear at relatively higher concentrations in the TSCCC analysis during the first 1000 to 2000 years; however, this is the transit time through the vadose zone which is not accounted for in the early release period of the TSCCC. Doses associated with this period of time are not a true representation of the system response. As the radionuclide half life becomes longer, the influence of the time-shift and decay calculation become insignificant. However, using the time-shift and decay calculation sequence will always result in a somewhat higher concentration and dose at peaks.

Attempting to discern the difference between the two analyses by superimposing the log-log plots of dose versus time may not be practical. Clearly, when peaks appear in the long-term portion of the analysis, (i.e., after 10,000 years in Figure 6 of the mid-June submittal to the PRP), the influence of short- to intermediate-half-life radionuclides is greatly diminished by this time and only the negligible differences in long-half-life radionuclides will be present. Thus, the width of the plotted line will mask the differences in the two cases when they are superimposed.

QUESTION 2. Is it possible by drawing groundwater from a well located 100-meter downgradient of the facility and in the heart of the plume, that other releases could converge downgradient of the 100-meter location and produce higher concentrations? Could lateral dispersion of adjacent plumes (from individual vault releases) yield higher concentrations?

RESPONSE 2. In locating the groundwater well and performing the analysis of water quality produced by a groundwater well we have followed 1) guidance from the PRP (Dodge, et al. 1991) on well location, and 2) guidance from the PATT (Wood, et al. 1992) on the calculation of groundwater well water quality.

PART 1. With respect to well location, in the performance assessment review guide (Dodge, et al. 1991; pg 2 of "Clarification of Requirements of DOE Order 5820.2A" issued February 28, 1989) DOE responded to the following question:

Question: Do the performance objectives apply to each LLW facility on a reservation or do they apply to the reservation as a whole? Also, what is the point of compliance?

Headquarter's response: The performance objectives are intended to apply to each LLW facility on a reservation rather than to the reservation as a whole. As recommended by the Peer Review Panel, the point of compliance should be no more than 100 meters from the waste.

Consequently, the Hanford staff adopted the 100-meter well location for the Hanford Grout PA, and did not examine other locations.

PART 2. Our calculation of groundwater quality as indicated by water withdrawn from a well follows the approach recommended by the PATT (Wood et al. 1992). The PATT examined the issue of "Groundwater Dose Objective and Compliance" and reached closure on an acceptable DOE complex-wide approach (Wood et al. 1992; pgs 22-23). In part, the PATT recommendation reads as follows:

... (groundwater) Protection should be defined in terms of the concentrations at the wellhead (or surface discharge zone, if applicable) for the appropriate drinking water or irrigation uses. Area-specific aquifer parameters, water use practices (i.e., well size, usage rate, and irrigation practices), and well-completion practices (i.e., screen depth and other appropriate parameters) may be used to define the effective (groundwater) source volume. (*Italics are mine.*)

Following this guidance, the Hanford staff determined irrigation rates (which determine pumping rate) and well screen intervals typical in the Hanford Site vicinity.

In the rationale given for their recommendation, the PATT expanded on the use of the screened interval length. It relates directly to the definition of the vertical distribution (i.e., dispersion) of contaminants. They reasoned that the length of screened opening defines the vertical thickness of the aquifer from which water is withdrawn, and that "this length could be used as a minimum unless modeling or measurements show that a greater vertical extent (of contamination) is reasonable." The PATT found in their brief survey of the DOE sites, the shortest screened interval in the DOE complex is that employed at the Hanford Site; 15 ft (approximately 5 m). This is the thickness of aquifer cross section that discharges contaminant.

In our analysis we assumed a vertical migration of contaminants from the vaults through the vadose zone. This limits the lateral

spread of contaminants in the vadose zone (lateral dispersion) to the land surface area of the facility. Vertical migration from an individual vault was modeled as occurring in a soil-sediment column defined by the symmetry of neighboring vaults. Hence, the vertical projection of the waste disposal facility onto the water table, when combined with the direction of groundwater flow beneath the facility, defines the width of contaminated groundwater plume. This is the width of aquifer cross section that receives contaminant. The plume width, the screened interval thickness, and the groundwater flow rate define the volume of groundwater receiving contaminant flux from the facility.

Effects of transverse dispersion in both the vadose zone and the aquifer were limited by the projected width of the facility on the groundwater flow. Essentially, by symmetry arguments, each vault simultaneously contributes the same average contaminant flux to the water table of the aquifer. By assuming vertical migration through the soil-sediment column, one has limited transverse dispersion within the vadose zone, even though travel through the vadose zone takes thousands of years under a surface recharge rate of 0.1 cm/yr. Once the contaminant enters the aquifer, travel time to the well located 100-m downgradient is quite short, i.e., 30 to 40 yr. Consequently, lateral spread of a contaminant plume, generated by a long-term release of the type envisioned from the facility, has been neglected because of the short distance and time involved. Certainly, any influence of lateral dispersion on contaminant concentration in the aquifer over a 30 to 40 year period and 100 meters is negligible in comparison to that which might occur during migration through the vadose zone.

By limiting lateral dispersive effects in the vadose zone to the land surface area of the facility, by limiting vertical dispersive effects in the aquifer to the 5-m screened interval of the well, and by neglecting lateral dispersion in the groundwater aquifer, we believe that contaminant concentrations are biased toward the conservative. In general, dispersive phenomena spread plumes and diminish peak contaminant concentrations. By limiting the influence of dispersive effects the modeling approach is biased toward producing higher peak concentrations.

It should be clear that the contaminant plumes from 33 individual vaults were not modeled separately in the Hanford Grout PA. We modeled the facility, all 33 vaults, as releasing simultaneously to the aquifer. Detailed heterogeneity, as reflected in the hydraulic properties of the vadose zone and unconfined aquifer, are not known at and below the scale of individual vaults. Consequently, the potential influence of different contaminant routes defined by a spatially varying advective process could not be and was not addressed. Based on guidance in PRP and PATT documents, the Hanford staff applied the modeling approach outlined above.

REFERENCES:

R.L. Dodge et al. 1991. Performance Assessment Review Guide for DOE Low-Level Radioactive Waste Disposal Facilities. DOE/LLW-93. Idaho National Engineering Laboratory, Idaho Falls, Idaho.

D.E. Wood et al. 1992. Performance Assessment Task Team Draft Progress Report. DOE/LLW-157, Rev.0. Idaho National Engineering Laboratory, Idaho Falls, Idaho.

Westinghouse
Savannah River Company

October 4, 1994

P.O. Box 616
Aiken, SC 29802
SRT-WED-94-0112

J.A. Turi, Director
Office of Program Integration
U.S. Department of Energy
Trevion II, EM-33
Washington, DC 20585-0002

Dear Mr. Turi:

PERFORMANCE ASSESSMENT PEER REVIEW PANEL RECOMMENDATIONS ON
THE "PERFORMANCE ASSESSMENT OF GROUTED DOUBLE-SHELL TANK
WASTE DISPOSAL AT HANFORD", WHC-SD-WM-EE-004, Rev. 0 (U)

The U. S. Department of Energy (DOE) Performance Assessment (PA) Peer Review Panel (PRP) has concluded its review of the subject PA and supplemental information. The Panel finding is that the analyses presented are technically adequate but that the approach taken is not consistent with the development and application of PA models around the DOE Complex.

The Panel recommends that the review by DOE Headquarters be completed and documented and that the PA be revised as discussed below prior to full implementation of the Grout program. When the PA is next revised, the Panel recommends that it be reviewed to ensure that the concerns with respect to consistency are addressed.

The Panel believes that limited implementation of the Grout program, such as use of the existing four vaults, could be considered as acceptable, based on the existing PA and supplemental information. However, full implementation of the Grout program, as stated above, should not be undertaken without revision and PRP review of the PA. Necessary elements of the revision are discussed below.

DISCUSSION

The Peer Review Panel met on September 27-29, 1994 to conclude the review of the Hanford Grout PA. At this meeting, the Panel reached the above finding. The attached chronology of documentation summarizes the review process and includes the supplemental information considered by the Panel in reaching the finding.

As defined by DOE Order 5820.2A and our charter, the PRP review focused on the technical adequacy, completeness and consistency of the modeling analyses, results, integration, and quality of documentation contained in the Hanford Grout PA and supplemental information. The PRP review addressed only the radioactive components of the waste analyzed and did not consider non-radioactive constituents.

J. A. Turi, EM-33

SRT-WED-94-0112

October 4, 1994

Page 2 of 4

The Panel concluded that the technical quality of work presented in the PA and supplemental information is sufficient to support a determination of compliance with the performance objectives of DOE Order 5820.2A. However, the approach taken in developing this PA is not consistent with the development and application of PA models around the DOE Complex.

Specifically, the guidance from the Peer Review Panel, and the direction taken by all of the other PAs that have been reviewed to date, is to first develop a conceptual model and then conduct the requisite analyses of that model. In the Hanford Grout PA, a variety of conceptual models, with respect to degradation of engineered barriers, were developed and analyzed. Then, a "Best Estimate Case" was developed which was not analyzed. Many of the conceptual models, or "Cases", analyzed differed in several details, making it very difficult to synthesize the results into an expected performance of the Grout Disposal Facility. While the Panel recognizes that, for complex engineered and/or natural systems, arriving at a single conceptual model might not be appropriate, it is nevertheless incumbent upon the assessors to follow through on each of the possible conceptual models to capture the results and then present the performance envelope for the system.

Therefore, the Panel could not find the Grout PA either "acceptable" or "unacceptable". In order to find the PA "acceptable", the Panel felt that a major revision would be needed and that the revision should be consistent with the guidance for preparing PAs. The Panel feels that the technical quality of the analyses presented in the PA and supplemental information is sufficient that the DOE Headquarters review should be completed and documented. However, the Panel also feels strongly that the lack of consistency of approach taken in the PA should be remedied by a complete revision followed by review by the Panel. This revision should be accomplished before full implementation of the grout program. Recommendations for the revision follow.

The Panel notes, for your information, that compliance is evaluated, in part, against draft DOE Order 5820.2B and RL Order 5820.2A instead of the existing DOE Order 5820.2A. Specifically, dose due to radon is excluded from the assessment of compliance with the intruder performance objective and radon emanation is evaluated versus the flux limit in draft DOE Order 5820.2B. Regulatory compliance with performance objectives is evaluated over a period of 1,000 years consistent with RL 5820.2A and compliance with programmatic design goals is considered over 10,000 years. DOE Order 5820.2A is silent with respect to the time for compliance and draft DOE Order 5820.2B specifies a 10,000 year compliance time.

SRT-WED-94-0112

October 4, 1994

Page 3 of 4

RECOMMENDATIONS FOR GROUT PA REVISION

The PRP recommends that the following elements be developed and incorporated into the Grout PA to make the approach consistent with the development and application of PA models around the DOE Complex and to improve the project documentation.

1. Incorporate all of the supplemental information provided to the Panel during the course of the review.
2. Formulate the most appropriate conceptual model, define the "Best Case", analyze it, and present the results of the analysis.
3. Provide justification for the selection of all parameters.
4. Conduct sensitivity analyses around the "Best Case" for all elements of the analysis, including the performance of engineered barriers. The following elements of the sensitivity analysis are now missing from the Grout PA and must be supplied in the revision:
 - a. Intruder parameters, such as the volume of soil into which contamination brought to the surface is mixed.

The PA, in the post-drilling garden scenario, assumes that the exhumed waste is mixed over an area of 2,500 m² to a depth of 15 cm (PA, page M.4). The resulting dose in this scenario is 72 mrem/year (PA, page 4.24). If the area over which the waste is mixed were reduced by about 30%, the resulting dose would exceed the performance objective of 100 mrem/year. However, the value of 2,500 m² is not supported in the PA; nor does the PA present the effect of varying the area.

- b. Vadose zone transport.

In the PA, variation of the properties of the vadose zone and saturated zone are represented as single values (Tables 3.42 and 3.44) without considering the potential effects of clastic dikes (discussed on page 3-15) or inhomogeneities in the vadose zone (Sections 2.1.6 and 2.1.7). The effect of these natural variations on disposal system performance is not addressed in the PA.

J. A. Turi, EM-33

SRT-WED-94-0112

October 4, 1994

Page 4 of 4

c. Saturated zone transport.

In the PA, the potential overlap of contaminant plumes from different vaults at distances greater than 100 meters is not considered. If the plumes were to overlap, maximum concentrations of contaminants may exceed the values determined at 100 meters.

5. Barrier degradation should be analyzed in a quantitative manner, where possible, rather than in a qualitative manner.
6. Sensitivity analyses should be computed rather than being estimated from the "Best Case" like the time-shifted case provided to the Panel to estimate the impact of earlier degradation.
7. The Interpretation of Results section should consider all of the above to arrive at an assessment of performance.

In closing, the Panel notes again the greatly improved quality of the Grout PA. The Panel also notes the highly cooperative and responsive attitude of the Hanford staff in responding to Panel inquiries. In particular, the participation and contributions of Dr. Charles Kincaid of PNL have greatly aided the completeness of the PA and the conduct of the review.

If you have any questions or comments on this review or on other aspects of the Panel's work, please call me.

Sincerely,

Elmer L. Wilhite, PRP Chairman
Advisory Scientist
Interim Waste Technology
Savannah River Technology Center
803-725-5800

cc: G. J. Duggan, EM-332
W. M. Levitan, EM-363
G. H. Sanders, RL
R. U. Curl, Lockheed Idaho
PRP Members and Advisors
W. E. Stevens, 773-A

J. V. Antizzo, EM-36
J. O. Boda, EM-363
G. F. Williamson, WHC
K. W. Owens, SAIC
D. E. Wood, WHC

Performance Assessment Peer Review Panel
Review of
Hanford Grout Performance Assessment,
Second Submittal

Chronology of Documentation

The following list of documents provides a complete chronology of the review of the second Hanford Grout Performance Assessment (PA) by the DOE PA Peer Review Panel (PRP).

- October, 1993, "Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford", WHC-SD-WM-EE-004, Rev. 0., Volumes 1 and 2.
- 10/11/93, R. J. Murkowski letter to L. Erickson, "RESPONSES TO PEER REVIEW PANEL COMMENTS ON GROUT PERFORMANCE ASSESSMENT", 9358786. (Documents response to PRP comments on the first Grout PA)
- 11/16/93, J. H. Anttonen, letter to J. A. Coleman, "RESPONSES TO PEER REVIEW PANEL COMMENTS ON THE PERFORMANCE ASSESSMENT OF GROUTED DOUBLE-SHELL TANK WASTE DISPOSAL AT HANFORD", TWD: LAH 93-DSB-048. (Transmits response to PRP comments on the first Grout PA to DOE HQ)
- 12/7/93, J. A. Coleman letter to Elmer Wilhite, "Review of 'Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford'". (Requests PRP review of the second Hanford Grout PA)
- 12/20/93, E. L. Wilhite letter to PRP members and advisors, "RADIOLOGICAL PERFORMANCE ASSESSMENT FOR HANFORD GROUT", SRT-WED-93-0069. (Transmits request for review to PRP)
- 1/12/94, E. L. Wilhite letter to PRP members and advisors, "RADIOLOGICAL PERFORMANCE ASSESSMENT FOR HANFORD GROUT", SRT-WED-94-0051. (Notifies PRP of completeness review meeting to be held on 2/9 & 10/94)
- 2/8/94, "ERRATA for Kincaid, et al., October 1993, Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford, WHC-SD-WM-EE-004, Rev. 0." (Errata provided to the PRP at the completeness review)
- 2/8/94, "Grout Inventory and Screening for Intruder Scenarios". (Supplemental tables showing intruder doses for all radionuclides in Grout inventory - provided to PRP at the completeness review)

DATE: 12-14-95 SRC: TSM DATE: 12-14-95
Hanford Grout PA Documentation Chronology

- 2/8/94, Revised chapter "7.0 References", dated February 1994. (provided to PRP at the completeness review)
- 2/9/94, "MINUTES OF THE SEVENTEENTH PERFORMANCE ASSESSMENT PEER REVIEW PANEL MEETING", RC-05-94, 4/5/94. (Documents completeness review held on 2/9 & 10/94)
- 2/15/94, E. L. Wilhite letter to J. A. Coleman, "REVIEW OF HANFORD GROUT PA", SRT-WED-94-0060. (Informs DOE-HQ of progress of review)
- 3/25/94, C. T. Kincaid letter to E. L. Wilhite, "Responses to Information Requested by the Peer Review Panel during the February 9-10, 1994 meeting in Dallas, Texas". (Attachments are: Revised Table 2.4 of WHC-SD-WM-EE-004, Rev.0, pages 2.52 - 2.55; "THE INVENTORY ROADMAP"; "INVENTORY DATA FLOW CHART"; "ADDITIONAL INFORMATION FOR DOSE ASSESSMENT"; "GROUT TREATMENT FACILITY WASTE FEED PROJECTIONS", WHC-SD-WM-TI-528, Rev.1, 2/94) (Documents information requested by the PRP.)
- 3/25/94, A. S. Icenhour letter to D. W. Lee, "A Review of the Performance Assessment of Grouted Double-Shell Tank Waste Disposal at Hanford". (Documents review by ORNL staff member, requested by D. W. Lee)
- 4/21/94, "MINUTES OF THE EIGHTEENTH PERFORMANCE ASSESSMENT PEER REVIEW PANEL MEETING", RC-10-94, 5/17/94. (Documents meeting to continue review of Grout PA)
- 4/26/94, E. L. Wilhite letter to G. F. Williamson, "REQUEST FOR ADDITIONAL INFORMATION FOR PRP REVIEW OF HANFORD GROUT PA", SRT-WED-94-0077. (Documents request for additional information relative to early barrier failure)
- 5/16/94, E. L. Wilhite letter to J. A. Turi, "CONTINUED REVIEW OF HANFORD GROUT PA & OTHER PRP ISSUES", SRT-WED-94-0079. (Informs DOE-HQ of progress of review)
- 6/16/94, C. T. Kincaid letter to G. F. Williamson. (Documents additional information requested by the PRP, which was distributed to the PRP at the 6/13/94 meeting. The material includes: Table 3.15, "Summary of Sorption Properties for Transport Groups in Grout and Soils/Sediments"; "RESPONSE TO QUESTIONS ON THE SECOND PRP INFORMATION REQUEST"; "RESPONSE TO THE SECOND PRP INFORMATION REQUEST", 10 June 1994)

Hanford Grout PA Documentation Chronology

- 7/14/94, C. T. Kincaid letter to E. L. Wilhite, "Response to requested clarification regarding Ru/Rh-106 doses shown in information dated 10 June 1994". (Provides clarification to information dated 6/10/94)
- 8/23/94, "MINUTES OF THE TWENTY-THIRD PERFORMANCE ASSESSMENT PEER REVIEW PANEL MEETING". (Documents meeting to continue Grout PA review.) [This set of minutes has not yet been issued.]
- 9/27/94, "MINUTES OF THE TWENTY-FOURTH PERFORMANCE ASSESSMENT PEER REVIEW PANEL MEETING". (Documents meeting to conclude Grout PA review. Includes the following attachments relative to the Grout PA: 1. C. T. Kincaid to S. M. Neuder, "Responses to questions posed by Stan Neuder, PRP member, Batelle Washington Office", 9/23/94. 2. D. W. Lee to E. L. Wilhite, 9/26/94, documents comments on clastic dikes.) [This set of minutes has not yet been issued.]