**Preliminary Design Report for
Modeling of Hydrogen Uptake in
Fuel Rod Cladding during
Severe Accidents**

L. J. Siefken

RECEIVED

SEP 14 1998

OSTI

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

August 1998

**Idaho National Engineering and Environmental Laboratory
Lockheed Martin Idaho Technologies
Idaho Falls, Idaho 83415**

LOCKHEED MARTIN

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Abstract

Preliminary designs are described for models of the interaction of Zircaloy and hydrogen and the consequences of this interaction on the behavior of fuel rod cladding during severe accidents. The modeling of this interaction and its consequences involves the modeling of seven processes: (1) diffusion of oxygen from the bulk gas into the boundary layer at the external cladding surface, (2) diffusion from the boundary layer into the oxide layer at the cladding external surface, (3) diffusion from the inner surface of the oxide layer into the metallic part of the cladding, (4) uptake of hydrogen in the event that the cladding oxide layer is dissolved in a steam-starved region, (5) embrittlement of cladding due to hydrogen uptake, (6) cracking of cladding during quenching due to its embrittlement and (7) release of hydrogen from the cladding after cracking of the cladding. An integral diffusion method is described for calculating the diffusion processes in the cladding. Experimental and theoretical results are presented that show the uptake of hydrogen in the event of dissolution of the oxide layer occurs rapidly and that show the release of hydrogen in the event of cracking of the cladding occurs rapidly. These experimental results are used as a basis for calculating the rate of hydrogen uptake and the rate of hydrogen release. The uptake of hydrogen is limited to the equilibrium solubility calculated by applying Sievert's law. The uptake of hydrogen is an exothermic reaction that accelerates the heatup of a fuel rod. An embrittlement criteria is described that accounts for hydrogen and oxygen concentration and the extent of oxidation. A design is described for implementing the models for Zr-H interaction into the programming framework of the SCDAP/RELAP5 code. A test matrix is described for assessing the impact of the Zr-H interaction models on the calculated behavior of fuel rods in severe accident conditions.

Table of Contents

1. Introduction.....	1
2. Oxygen Transport and Dissolution of Oxide Layer.....	2
3. Hydrogen Uptake in Cladding	12
4. Cladding Cracking and Hydrogen Release.....	17
5. Implementation of Zr-H Interaction Models.....	23
6. Testing and Assessment of Zr-H Interaction Models	25
7. Summary.....	26
8. References.....	27
Appendix A.....	A-1

List of Figures

Figure 1. Radial distribution of oxygen in the bulk gas and in the cladding.	2
Figure 2. Simplified Zr-O phase diagram with homogenized oxide and metal phases.	3
Figure 3. Rate of hydrogen uptake as function of temperature as measured by Steinbruck, et al.	14
Figure 4. The zirconium-hydrogen phase diagram.	17
Figure 5. Crack formation in preoxidized Zircaloy during rapid cooldown from 1200 C by steam.	18
Figure 6. Crack formation in preoxidized Zircaloy during rapid cooldown from 1400 C by steam.	19
Figure 7. Temperature history and corresponding hydrogen release history.	20
Figure 8. Implementation of Zr-H interaction models into frame work of SCDAP/RELAP5 programming.	23

List of Tables

Table 1. Definition of symbols in Figure 1.....	2
Table 2. Period of hydrogen uptake (parameter t_{eq}) as a function of temperature	15
Table 3. Conditions for example calculation of rate of generation due to hydrogen uptake.....	16
Table 4. Model for determining whether cladding is embrittled.....	19
Table 5. Matrix of test problems for assessing models for Zr-H interaction and its consequences	25

1. Introduction

Experimental and theoretical results have shown that the behavior of fuel rods during a severe accident may be significantly influenced by the uptake of hydrogen in the fuel rod cladding in the regions of the reactor core with a hydrogen-rich (steam-starved) environment. The uptake of H_2 does not begin until the oxide layer dissolves into the metallic layer. This dissolution process results from a hydrogen-rich environment at the outer surface of the oxide layer. The uptake of hydrogen may cause a heatup of the cladding that is of the same order of magnitude as that caused by oxidation. The uptake of hydrogen may embrittle the fuel rod cladding and make it vulnerable to cracking during a core reflood. In a steam-rich environment, the cracking of the cladding results in a release of hydrogen from the cladding to the bulk fluid. SCDAP/RELAP5/MOD3.2¹ has no models for hydrogen uptake and hydrogen release or for evaluating the vulnerability to cracking caused by hydrogen uptake. Preliminary designs for models of these aspects of fuel rod behavior are proposed in this report.

This report is organized as follows. A model for calculating the time at which a ZrO_2 layer may disappear due to dissolution of oxygen into the adjoining metallic layer is described in Section 2. This model applies the integral diffusion method to calculate the diffusion of oxygen from the bulk gas into the cladding oxide layer and then into the cladding metallic layer. Section 3 describes the model for calculating the rate of hydrogen uptake and the resulting heat generation following the disappearance of the oxide layer. A model for evaluating the vulnerability of the cladding to cracking due to embrittlement caused by hydrogen uptake is described in Section 4. This section also describes a model for calculating the rate of release of hydrogen after cracking of the cladding. A design for implementation of the Zr-H interaction models into the programming framework of SCDAP/RELAP5 is described in Section 5. A test matrix for assessing the models for hydrogen uptake and its consequences is presented in Section 6. A summary of the Zr-H interaction models is presented in Section 7 and the references are listed in Section 8.

2. Oxygen Transport and Dissolution of Oxide Layer

Hydrogen uptake occurs after the oxide layer at the cladding outer surface dissolves into its adjoining metallic layer. This event can happen when a relatively thin oxide layer exists in a steam-starved environment for a period of time. The calculation of this event in turn requires the calculation of the transport of oxygen from the bulk gas to the oxide layer and then from the oxide layer to the metallic layer. Figure 1 shows schematically the oxygen distribution in the gas boundary layer, cladding oxide

Figure 1. Radial distribution of oxygen in the bulk gas and in the cladding.

layer, and cladding metallic layer. The symbols in Figure 1 are defined in Table 1.

Table 1. Definition of symbols in Figure 1.

Symbol	Units	Definition
y_i	-	mole fraction of H_2O in bulk gas at axial node i
y_s	-	mole fraction of H_2O in gas at outer surface of oxide layer
C_s	-	O/Zr ratio at external surface of oxide layer
C_a	-	O/Zr ratio at inner surface of oxide layer; $C_a = 1.985$ for temperature less than 1773 K, $C_a = 1.72$ for temperature greater than 1773 K.
C_b	-	O/Zr ratio at outer surface of metallic layer (terminal solubility)
δ	m	Thickness of oxide layer
ξ	m	thickness of metallic layer
ξ_0	m	thickness of as-fabricated cladding
x'	m	spatial coordinate for oxide layer
x	m	spatial coordinate for metallic layer

The overall oxygen transport is calculated by coupling the equations that calculate the diffusion of oxygen through the three layers shown in Figure 1. The method of solution as derived by Olander² will be used. The oxygen transport is governed to a significant extent by the phase diagram for the Zr - O system. Figure 2 shows the simplified phase diagram that will be employed. The symbols in this figure are the

Figure 2. Simplified Zr-O phase diagram with homogenized oxide and metal phases.

same as those defined in Table 1. In a steam-rich environment, C_s equals 2.00 and the outer surface is stoichiometric oxide ZrO_2 . In a steam-starved environment, y_s may be small enough that C_s is less than 2.00. When C_s is reduced in value to the O / Zr ratio of the lower phase boundary of zirconia ($C_s = C_a$ as shown in Figure 2), the oxide layer gradually dissolves into the metallic layer and eventually may completely disappear. When this occurs, hydrogen begins to diffuse into the metallic layer.

The equations for calculating the oxygen diffusion through the three layers shown in Figure 1 are described next.

The flux of water vapor through the gas boundary layer is calculated by the equation

$$\dot{w} = k_g C_g (y_i - y_s) \quad (1)$$

where

$$\begin{aligned} \dot{w} &= \text{mass flux of oxygen through the gas boundary layer } (kg - moles/m^2 \cdot s), \\ k_g &= \text{mass transfer coefficient (m/s),} \end{aligned}$$

C_g	=	molar density of the bulk gas $(p_{tot}/RT)(\text{kg-mole}/\text{m}^3)$,
p_{tot}	=	total pressure of the bulk gas (Pa).
R	=	universal gas constant $(\text{Pa} \cdot \text{m}^3/\text{kg-mole} \cdot \text{K})$,
T	=	temperature of bulk gas (K),
y_i	=	mole fraction of H_2O in the bulk gas at location of axial node i ,
y_s	=	mole fraction of H_2O in the gas at the cladding outer surface.

The mass transfer coefficient k_g is calculated using the analogy between heat and mass transfer. According to this analogy,

$$k_g = \frac{\text{Nu} D_g}{d_h} \quad (2)$$

where

Nu	=	Nusselt number of the bulk gas $\left(\frac{h d_h}{k_v}\right)$,
h	=	convective heat transfer coefficient $(\text{W}/\text{m}^2 \cdot \text{K})$,
D_g	=	binary diffusivity in $\text{H}_2\text{O} + \text{H}_2$ mixture (m^2/s) ,
d_h	=	hydraulic diameter (m),
k_v	=	thermal conductivity of water vapor $(\text{W}/\text{m} \cdot \text{K})$.

The variable D_g will be calculated by the model for mass diffusivity that is currently in SCDAP/RELAP5¹. This model is applicable to gas mixtures composed of several species. An alternative model for a mixture of H_2O and H_2 is presented in Appendix A.

The diffusion of oxygen through the gas boundary layer and then through the oxide layer can be regarded as two steps in series. Thus, diffusion through the two layers is equal and expressed by the equation

$$\dot{w} = \rho_{ox} D_{ox} (C_s - C_a) / \delta \quad (3)$$

where

ρ_{ox}	=	molar density of Zr in ZrO_2 $(\text{kg-mole}/\text{m}^3)$ $(47 \text{ kg-mole}/\text{m}^3)$,
D_{ox}	=	diffusion coefficient of oxygen in the oxide layer (m^2/s) .

The correlation to be used for D_{ox} is given in Appendix A.

The value of C_s in Equation (3) is very close to the value of 2.0 as long as the gas at the cladding surface contains at least a small fraction of water vapor. Thus, for usual applications, Equations (1) and (3) can be combined to give

$$y_s = y_i - \frac{D_{Ox} \rho_{Ox} (2 - C_a)}{k_g C_g \delta} \quad (4)$$

When y_s as calculated by Equation (4) is negative, then the oxygen uptake is limited to the flux through the gas boundary layer as given by Equation (1) with y_s equal to 0.0. Thus for this condition, C_s is given by the equation

$$C_s = C_a + \frac{k_g C_g y_i \delta}{\rho_{Ox} D_{Ox}} \quad (5)$$

The overall mass balance on zirconium is given by the equation

$$\xi_o = \xi_1 + G\delta_o = \xi + G\delta \quad (6)$$

where

ξ_o	=	as-fabricated thickness of cladding (m),
ξ_1	=	thickness of metallic layer at time of 0.0 (m),
δ_o	=	thickness of oxide layer at time of 0.0 (m),
ξ	=	thickness of metallic layer at time of t (m),
δ	=	thickness of oxide layer at time of t (m),
G^{-1}	=	Pilling-Bedworth ratio of ZrO_2 ($G=0.67$).

Oxygen transport in the metallic layer is governed by Fick's law, with a convective term that accounts for the moving oxide-metal interface. Fick's law is expressed by the equation

$$\frac{\partial c}{\partial t} = D_m \frac{\partial^2 c}{\partial x^2} + G \frac{d\delta}{dt} \frac{\partial c}{\partial x} \quad (7)$$

where

c	=	O/Zr ratio in the metallic layer at time t and at radial coordinate x,
x	=	distance from moving interface, as shown in Figure 1 (m),
t	=	time (s),
D_m	=	diffusion coefficient of oxygen in α - Zr (m^2/s).

The initial and boundary conditions for the above equation are

$$c(x, 0) = c_0 \quad (8)$$

$$c(0, t) = C_b \quad (9)$$

$$\frac{\partial c(\xi, t)}{\partial x} = 0.0 \quad (10)$$

The correlation to be used for D_m is given in Appendix A.

The integral diffusion method is applied by integrating Equation (7) with respect to x over the thickness of the metallic layer. The integration is performed over the domain ($0 < x < \xi$). The result of this integration is

$$\frac{d}{dt}(\xi \bar{c}) = D_m \left[\left(\frac{\partial c}{\partial x} \right)_{\xi} - \left(\frac{\partial c}{\partial x} \right)_0 \right] + G \frac{d\delta}{dt} [c(\xi, t) - C_b] \quad (11)$$

where

$$\bar{c} = \text{average O/Zr ratio in the metallic layer.}$$

The variable $\bar{c}$ is calculated by the equation

$$\bar{c} = \frac{1}{\xi} \int_0^{\xi} c(x, t) dx. \quad (12)$$

Equation (11) is converted to an ordinary differential equation by choosing an approximate distribution $c(x, t)$ that automatically satisfies the boundary conditions as expressed by Equations (9) and (10) and contains a single time-dependent parameter whose value at $t = 0$ is chosen to satisfy the initial conditions as expressed by Equation (8). Such an approximate distribution is given by the function

$$c = C_b \frac{\exp(-\phi/E) \exp\{-(1-\phi)/\delta\}}{1 + \exp(-1/E)}$$

$$\phi = \frac{x}{2\xi} \quad 0 \leq \phi \leq \frac{1}{2}. \quad (13)$$

The variable E is a function of time and it is evaluated by the relationship between E and the average O/Zr ratio in the metallic layer. This relationship is obtained by substituting Equation (13) into Equation (12). The result of this substitution is

$$\frac{\bar{c}}{C_b} = 2E \frac{1 - \exp(-1/E)}{1 + \exp(-1/E)}. \quad (14)$$

The rate of movement of the inside surface of the oxide layer is equal to the difference between the oxygen flux on the outside surface of the metallic layer and the oxygen flux on the inside surface of the oxide layer. This relation is expressed by the equation

$$\rho_{ox}(C_a - C_b) \frac{d\delta}{dt} = \rho_m D_M \left(\frac{\partial c}{\partial x} \right)_o - \rho_{ox} D_{ox} \left(\frac{\partial c'}{\partial x'} \right)_\delta \quad (15)$$

where

$$\left(\frac{\partial c}{\partial x} \right)_o = \text{O/Zr gradient in the metallic layer at its interface with the oxide layer,}$$

$$\left(\frac{\partial c'}{\partial x'} \right)_\delta = \text{O/Zr gradient in the oxide phase at its interface with the metallic layer,}$$

$$\rho_m = \text{molar density of Zr in the metallic layer (kg-mole/m}^3\text{).}$$

The value of ρ_m is given by the equation

$$\rho_m = \rho_{ox} / G = \rho_{ox} / 0.67. \quad (16)$$

The oxygen concentration distribution in the oxide layer is assumed to be linear. Thus the variable $(\partial c' / \partial x')_\delta$ in Equation (15) is given by the equation

$$\left(\frac{\partial c'}{\partial x'} \right)_\delta = (C_a - C_b) / \delta. \quad (17)$$

Substituting Equation (17) into Equation (15), replacing ρ_m with its equivalent of ρ_{ox} / G , and evaluating the oxygen concentration gradient at $x = 0$ in Equation (15) using Equation (13) yields the equation

$$G(C_a - C_b) \frac{d\delta}{dt} = -\frac{D_m C_b}{4E^2 \xi} \left(\frac{\bar{c}}{C_b} \right) + \frac{G D_{ox}}{\delta} (C_s - C_a). \quad (18)$$

Equations (18), (6), (11), and (14) are a coupled set of equations for solving for the unknown variables δ , ξ , $\bar{c}$, and E , respectively.

The calculated value of δ is used to determine whether Zr-H reaction begins in the cladding. If δ is greater than zero, then the oxide layer insulates the metallic layer from the hydrogen in the bulk gas. If δ is equal to zero, then hydrogen diffuses into the metallic layer.

The integral solution method will next be presented for calculating oxygen transport in the other two possible states of the cladding, namely the state of no oxide layer being present and the state of no metallic layer being present. With the description of the solution for these states, the integral method is shown to be applicable to all possible states of the cladding.

In the event that the oxide layer has dissolved completely into the metallic layer and is no longer present, the oxygen transport in the metallic layer is then governed by the equation

$$\frac{\partial c}{\partial t} = D_m \frac{\partial^2 c}{\partial x^2}. \quad (19)$$

The boundary condition for Equation (19) at the outer surface of the metallic layer is the oxygen flux through the gas phase boundary. This boundary condition is expressed by the equation

$$k_g C_g y_i = -D_M \rho_M \left(\frac{\partial c}{\partial x} \right)_0. \quad (20)$$

At the inner surface of the metallic layer, the zero flux condition applies, i.e.

$$\left(\frac{\partial c}{\partial x} \right)_{\xi_0} = 0. \quad (21)$$

The initial condition for Equation (19) is the oxygen distribution in the metallic layer at the time that the oxide layer just disappeared. The integral method will also be applied to solve for Equation (19). The approximate distribution in oxygen as defined by Equation (13) is adopted for the solution of Equation (19) with the terminal oxygen solubility at the outer surface of the metallic layer (variable C_b in Equation (13)) replaced by the undetermined function $c(0,t)$:

$$c = c(0,t) \frac{\exp(-\phi/E) + \exp\{-(1-\phi)/E\}}{1 + \exp(-1/E)} \quad (22)$$

where

$$\phi = \frac{x}{2\xi_0} \quad 0 \leq \phi \leq \frac{1}{2}.$$

The average oxygen concentration in the metallic phase is thus given by the equation

$$\frac{\bar{c}}{c(0,t)} = 2E \frac{1 - \exp(-1/E)}{1 + \exp(-1/E)}. \quad (23)$$

Substituting the approximate oxygen distribution as given by Equation (23) into Equation (20) and using Equation (23) to eliminate the surface concentration fixes the parameter E according to

$$E = \left\{ \frac{D_M \rho_M C_b}{4 \xi_0 k_g C_g y_i} \left(\frac{\bar{c}}{C_b} \right) \right\}^{1/2}. \quad (24)$$

The concentration of oxygen at the external surface of the metallic layer can be determined by solving Equation (23) for $c(0,t)$. The result is

$$\frac{c(0,t)}{C_b} = \frac{(\bar{c}/C_b)1 - \exp(-1/E)}{2E1 + \exp(-1/E)}. \quad (25)$$

Finally, the integration with respect to x over the domain ($0 < x < \xi_0$) results in the equation

$$\frac{d}{dt}\left(\frac{\bar{c}}{C_b}\right) = \frac{k_g C_g y_i}{\rho_M \xi_o C_b}. \quad (26)$$

Equations (24) and (26) are a set of two coupled equations for solving for the two variables E and $\bar{c}$, respectively. Equation (25) is also applied at each time step to determine whether the surface concentration $c(0,t)$ has returned to the terminal solubility C_b . If the value of the right hand side of Equation (25) is greater than unity, then $c(0,t)$ has exceeded the surface solubility and the oxide layer forms again.

The case of an oxide layer propagating to the inner surface of the cladding is presented next. The time at which the oxide layer propagates to the inner surface is designated by the symbol t_{sw} . The average O/Zr ratio in the oxide layer and the oxygen concentration gradient through the oxide layer are given by the equations

$$\bar{c}' = \frac{1}{2}(C_s + C_a), \quad (27)$$

$$\frac{dc'}{dx'} = \frac{C_s - C_a}{\xi_o/G}. \quad (28)$$

For $t > t_{sw}$, the oxygen concentration distribution through the oxide layer is no longer linear. The gradient of the oxygen concentration distribution at the inner surface of the cladding is given by the equation

$$\left(\frac{\partial c'}{\partial x'}\right)_{\xi_o/G} = 0. \quad (29)$$

To track the approach of the oxide layer to complete conversion of stoichiometric ZrO_2 , the oxygen concentration distribution through the oxide layer is assumed to be approximated by the following function:

$$c' = C_s - a\left(\eta + \frac{1}{2}\eta^2 - \frac{2}{3}\eta^3\right) \quad (30)$$

where

$$\eta = \frac{x'}{\xi_o/G}$$

In Equation (30), the variable "a" is a function of time that is to be determined. Equation (31) has only one minimum for positive values of η , and that occurs at $\eta = 1$, which results in the boundary condition for the inner surface of the cladding being satisfied as expressed by Equation (29).

The average oxygen concentration in the oxide layer as given by Equation (30) is given by the equation

$$\bar{c}' = \int_0^1 c' d\eta = C_s - \frac{1}{2}a. \quad (31)$$

The gradient in the oxygen concentration at the outer surface of the oxide layer is given by the equation

$$\left(\frac{dc'}{d\eta}\right)_0 = -a. \quad (32)$$

Equation (32) satisfies Equation (28) when the function $a(t)$ at time t_{sw} has the following value;

$$a(t_{sw}) = C_s - C_a. \quad (33)$$

Oxygen diffusion in the oxide layer is governed by Fick's law as expressed by the equation

$$\frac{\partial c'}{\partial t} = D_{ox} \frac{\partial^2 c'}{\partial x'^2}. \quad (34)$$

Equation (34) can be integrated with respect to x' over the domain of the cladding thickness ($0 < x' < (\xi_0 / G)$). The oxygen concentration gradients at the inner and outside surfaces of the oxide layer are calculated from Equations (29) and (32), respectively. The result is an ordinary differential equation for the variable $a(t)$, which is expressed by the equation

$$\frac{da}{dt} = \frac{2D_{ox}}{(\xi_0/G)^2} a \quad t \geq t_{sw}. \quad (35)$$

The initial condition for Equation (35) is given by Equation (33). Since the variable D_{ox} varies with temperature and thus in severe accident conditions varies with time, Equation (35) cannot be directly integrated.

The oxygen uptake rate is determined from the solution of Equation (35) in conjunction with

$$\dot{w} = -\rho_{ox} D_{ox} \left(\frac{\partial c'}{\partial x'}\right)_0 = -\frac{\rho_{ox} D_{ox}}{\xi_0/G} \left(\frac{dc'}{d\eta}\right)_0 = \frac{\rho_{ox} D_{ox}}{\xi_0/G} a. \quad (36)$$

A complete set of equations have now been expressed for calculating oxygen diffusion through the cladding for the three possible phase states of the cladding.

The integral method for calculating oxygen uptake is more accurate than the parabolic kinetics method for the case of steam starvation and transient temperature.² Since the integral method is necessary for calculating the time at which hydrogen uptake begins, its implementation for this purpose also results in a complete calculation of cladding oxidation. Thus, the option exists for replacing the existing parabolic kinetics modeling of cladding oxidation with the integral solution method. As described further in Section 5, an input option will be implemented that provides the capability to compare the accuracy and robustness of these two methods of solution.

3. Hydrogen Uptake in Cladding

The disappearance of the cladding oxide layer in a region of the reactor core with hydrogen-rich fluid results in the diffusion of hydrogen into the cladding. The calculation of the time that the oxide layer may disappear has been presented in Section 2. This section presents a set of equations that can be solved to calculate the uptake of hydrogen in the cladding. Equations are also presented for calculating the effect of hydrogen uptake on fuel rod heatup.

A simplified approach to calculating the rate of hydrogen uptake is proposed that capitalizes on the numerical results of detailed calculations. A detailed modeling of hydrogen uptake involves the coupling of several phenomena; (1) diffusion of hydrogen from the fluid adjoining the external surface of the cladding through the cladding and into the fuel-cladding gap, (2) ternary diffusion of a mixture of Xe, He, and H₂ in the axial direction through the fuel-cladding gap and then through the breach in the cladding caused by cladding rupture, (3) release from fuel of Xe, and (4) diffusion of He from the upper fuel rod plenum into the fuel-cladding gap.³ Calculations have shown that the hydrogen uptake occurs rapidly until the equilibrium solubility of the cladding is attained. In a calculation with conditions typical of a severe accident, the hydrogen uptake to the equilibrium solubility occurred in about 50 s.³ This period of time is small compared with the period of time for evolution of the important damage progression events occurring during a severe accident. The rate of hydrogen permeation of the cladding was calculated to be much greater than the rate of diffusion of hydrogen from the breach site. Also, the amount of hydrogen that can be absorbed by the fuel-cladding gap is small compared to the amount of hydrogen that can be absorbed by the cladding. In view of the short time period for hydrogen uptake and in view of the relatively small effect of hydrogen absorption and diffusion in the fuel-cladding gap, the modeling of the axial diffusion of hydrogen through the fuel-cladding gap and then its diffusion out of the breach site is not justified. Therefore, a simplified approach to calculating hydrogen uptake will be taken.

The equilibrium solubility of hydrogen in the Zircaloy is assumed to be governed by Sievert's law.⁴ According to Sievert's law for Zr-H interaction, the equilibrium solubility is given by the equation

$$C_H = A_{SH} \exp\left(-\frac{\Delta H_H}{RT}\right) (p_{H_2})^{0.5} \quad (37)$$

where

C_H	=	H/Zr ratio of the metal in equilibrium with the gas containing H ₂ at a pressure of p_{H_2} .
A_{SH}	=	Sievert's law constant which is a function of temperature.
ΔH_H	=	enthalpy of solution (kcal/mol).
R	=	universal gas constant (1.987 cal/mole · K).
T	=	temperature of cladding (K).
p_{H_2}	=	partial pressure of hydrogen (atm).

Sievert's law constant is given by the equation⁴

$$A_{SH} = e^{\Delta S/R} \quad (38)$$

where

$$\Delta S = \text{entropy of solution of hydrogen in zirconium (cal/mol} \cdot \text{K)}.$$

According to experimental results obtained by Moalem and Olander⁴, the entropies and enthalpies of solution of hydrogen in zirconium vary somewhat with the oxygen content and the phase (α or β) of the zirconium. Representative values for severe accident analysis are:

$$\Delta S = -12.5 \quad (39)$$

and

$$\Delta H = -13.1. \quad (40)$$

Since the enthalpy of solution (ΔH) is negative, the Zr-H₂ reaction is exothermic and thus causes an increase in the heatup of the cladding.

Substituting the values ΔS and ΔH given by Equations (39) and (40) into Equations (38) and (37) results in the following equation for C_H :

$$C_H = 1.85 \times 10^{-3} \exp(6593/T)(p_{H_2})^{0.5}. \quad (41)$$

For cladding at a temperature of 2000 K and a hydrogen pressure of 0.1 MPa (1 atm), the value of C_H as calculated by Equation (41) is 0.05. For cladding at a temperature of 2000 K and a hydrogen pressure of 3 MPa (30 atm), the value of C_H is 0.27. For cladding at a temperature of 1273 K and a hydrogen pressure of 0.1 MPa (1 atm), the value of C_H is 0.33.

The rate of hydrogen uptake after disappearance of the oxide layer is based on Olander's numerical results³ and not upon mechanistic modeling. According to Olander's numerical results, the hydrogen uptake for conditions of a typical severe accident attains an equilibrium level in ~ 50 s. This calculated rate of hydrogen uptake is consistent with the rate of hydrogen uptake measured by Steinbruck, et al.⁵ The hydrogen uptake is assumed to follow a parabolic kinetics rule. The change in cladding temperature during the period of hydrogen uptake is assumed to be small. Thus, the rate of hydrogen uptake is assumed to be given by the equation:

$$\frac{dw_h}{dt} = \frac{K_h}{w_h} \quad (42)$$

where

w_h = uptake of hydrogen (ratio of hydrogen concentration in cladding to hydrogen concentration at equilibrium level),

K_h = parabolic kinetics constant for uptake of hydrogen (1/s),

t = time (s).

The integration of Equation (43) results in the equation

$$w_h = [2K_h(t - t_{dis})]^{0.5} \quad (43)$$

where

t_{dis} = time at which the oxide layer on the external cladding surface disappeared (s).

The value of w_h at the equilibrium concentration of hydrogen is C_H as calculated by Equation (42). The time to attain an equilibrium level of hydrogen concentration is assumed to be t_{eq} . Substituting these values into Equation (44) and solving for K_h , the result is:

$$K_h = \frac{C_H^2}{2t_{eq}} \quad (44)$$

The value t_{eq} is a function of temperature. The approximate dependence of t_{eq} on temperature has been investigated by Steinbrück, et al.⁵ Figure 3 is a plot of the rate of hydrogen uptake as a function of

Figure 3. Rate of hydrogen uptake as function of temperature as measured by Steinbrück, et al.

temperature as measured by Steinbrück, et al. The approximate value of t_{eq} as indicated by the experimental results is shown in Table 2. For cladding at a temperature of 1730 K, the value of t_{eq} is 30 s.

For cladding at a temperature of 1435 K, the value of t_{eq} is 120 s. For temperatures between the temperature values shown in Table 2, the value of t_{eq} will be found by linear interpolation.

Table 2. Period of hydrogen uptake (parameter t_{eq}) as a function of temperature.

Cladding temperature (K)	t_{eq} (s)
<1240	300
1240	300
1340	200
1435	120
1540	60
1640	40
1730	30
1730	30

The uptake of hydrogen is an exothermic reaction that accelerates the heatup of the fuel rod. The heatup due to hydrogen uptake is calculated by the equation:

$$\dot{Q}_H = -2\pi r_o \Delta z \xi_o \rho_M \Delta H_{HSI} (C_{H2} - C_{H1}) / \Delta t \quad (45)$$

where

$\dot{Q}_H$	=	rate of heat generation at an axial node due to uptake of hydrogen (W),
r_o	=	radius of external surface of cladding (m),
Δz	=	height of axial node (m),
ρ_M	=	molar density of Zr in zircaloy ($k_g \cdot mol/m^3$),
ξ_o	=	as-fabricated thickness of cladding (m),
ΔH_{HSI}	=	enthalpy of solution in SI units ($J/k_g \cdot mole$),
C_{H2}	=	H/Zr ratio in cladding at end of time step,
C_{H1}	=	H/Zr ratio in cladding at start of time step,
Δt	=	time step (s).

The enthalpy of solution, ΔH_H , has a value of -13.1 kcal/mol³ for beta phase cladding with a O/Zr ratio of 0.2. Converting the units of the enthalpy of solution to SI units, the result is:

(46)

$$\Delta H_{HSI} = -3.129 \times 10^6 \quad (47)$$

where

$$\Delta H_{HSI} = \text{enthalpy of solution (J/kg-mol)}.$$

The enthalpy of solution varies slightly with variation in the O/Zr ratio of the cladding.

The rate of heat generation due to hydrogen uptake is calculated to not be as significant as implied by Olander.³ Given the typical severe accident conditions as defined in Table 3, Equations (41) and (45) calculate that the average rate of heat generation due to hydrogen uptake through the period of hydrogen uptake is only 36 W/m. This rate of heatup is small compared to the rate of heat generation due to oxidation under these same conditions, which is calculated to be about 400 W/m.

Table 3. Conditions for example calculation of rate of heat generation due to hydrogen uptake

Variable	Units	Value
P_{H2}	MPa	3.0
T	K	2000
r_0	m	4.8×10^{-3}
Δz	m	1.
ξ_0	m	0.6×10^{-3}
ρ_m	kg-mol/m ³	70.5
ΔH_{HSI}	J/kg-mol	-3.129×10^6
$C_{H2} - C_{H1}$	H/Zr ratio	0.27
Δt	s	50.

After the hydrogen concentration has reached the solubility limit (equilibrium level), the further heatup of the cladding results in a reduction in solubility and thus a release of hydrogen. The desorption of hydrogen is endothermic and results in the cladding functioning as a heat sink.

4. Cladding Cracking and Hydrogen Release

Hydrogen may be stored in the cladding due to hydrogen uptake during a period of steam-starved oxidation^{6,7} and then be released during a quenching period when the cladding may crack due to thermal stresses in cladding embrittled by a combination of oxygen and hydrogen uptake.^{7,8} The embrittlement of the cladding decreases its ductility to the point that the stresses induced by a temperature gradient during quenching may result in cracking of the cladding. So the existing model in SCDAP/RELAP5 for determining when the cladding cracks needs to be extended to account for the effect of hydrogen uptake on the structural integrity of the cladding during a reflood of the reactor core. The model will be applied to determine the time at which the cladding at any location may crack to the extent that hydrogen absorbed in the metallic phase of the cladding is released and oxygen from the coolant may contact the inner surface of the cladding.

A model accounting for the effect of hydrogen uptake on structural integrity will be presented that is based on the results of experiments that involved the reflood of hot fuel rods. Neither a theoretical model or a broadly-based empirical model appropriate for SCDAP/RELAP5 were found in the literature. The phase diagram for the Zr-H system as shown in Figure 4 provides an indication of the ranges of

Figure 4. The zirconium-hydrogen phase diagram.

temperature and hydrogen concentration in which the cladding may be embrittled. The Appendix K⁹ embrittlement criteria defines the cladding to be embrittled when it is more than 17% oxidized. This criteria is considered to have enough conservatism that the additional embrittlement due to hydrogen uptake does not need to be taken into account.⁸ Its conservatism does not make it appropriate for SCDAP/RELAP5. The Chung and Kassner embrittlement model¹⁰ defines cladding to be embrittled when the

thickness of the beta phase of the cladding is less than 0.1 mm and the concentration of hydrogen in the metal phase is less than 20 at.% (2200 ppm). Recent experimental results indicate that this model may not account fully for the effect of hydrogen concentration on embrittlement and that it may not be applicable for rapid cooling in a steam environment such as may occur above a quench front.⁷ So an extension of existing models for embrittlement to account for hydrogen uptake will be developed as follows. First, experimental results will be compiled that present a picture of the effect of the thickness of the cladding oxide layer and hydrogen concentration on cladding integrity during reflood. Then, an extension will be made to the Chung and Kassner model to account for these experimental results.

Experimental results applicable for evaluating the structural integrity of fuel rods during quenching are available from several sources. Results from the QUENCH program at the Forschungszentrum in Karlsruhe, Germany for fuel rods quenched from maximum temperatures of 1473 K and 1673 K are shown in Figure 5

Figure 5. Crack formation in preoxidized Zircaloy during rapid cooldown from 1200° C by steam.

and Figure 6, respectively.⁷ The crack density data shown in these figures apply to the rapid cooling in steam (~50 K/s) of fuel rods that were heated in a steam environment to temperatures in the range of 1473 K to 1673 K. As shown in these figures, oxide layer thicknesses less than 0.15 mm did not result in cracking of the cladding. Oxide layer thicknesses in the range 0.15 mm to 0.225 mm resulted in axial cracks in the cladding that penetrated through the wall of the cladding. Oxide layer thicknesses greater than 0.225 mm resulted in both axial and circumferential cracks in the cladding. The threshold oxide layer thickness for occurrence of circumferential cracks increases somewhat with an increase in the cladding temperature at the start of cooldown. Experiments performed at Argonne National Laboratory on the quenching of hot and partially oxidized fuel rods indicated that cracking of the cladding did not occur provided that the thickness of the beta phase of the cladding was greater than 0.1 mm and the hydrogen concentration was less than 20 at.%.¹⁰ These experiments quenched the fuel rods with water and involved cooling rates of order of 100 K/s. Experiments performed in the Power Burst Facility at the Idaho National Engineering and Environmental Laboratory on the quenching of hot and partially oxidized fuel rods indicated that cracking of the cladding may occur during quenching when the hydrogen concentration in the cladding exceeds 10 at.%.¹¹ These experiments also quenched the fuel rods with water and involved cooling rates of order of 100 K/s. Experiments performed at the Japan Atomic Energy Research Institute in Japan on the quenching of

Figure 6. Crack formation in preoxidized Zircaloy during rapid cooldown from 1400° C by steam.

cladding under reflood conditions for large break Loss of Coolant Accidents indicate that hydrogen concentrations in excess of 20 at.% may contribute to the embrittlement of the cladding.⁸

The experimental results can be used as a basis for extending the Chung and Kassner embrittlement model to account for hydrogen concentration and thickness of oxide layer. The extended embrittlement model is defined in Table 4. Blank column entries in a row indicate that embrittlement for that row is not a function of those column entries. As shown in Table 4, cladding with an oxide layer greater than 0.2 mm in

Table 4. Model for determining whether cladding is embrittled

beta phase thickness	oxide layer thickness	hydrogen concentration	embrittled?
(mm)	(mm)	at. %	yes/no
>0.1	<0.2	<10	no
<0.1	-	-	yes
-	>0.2	-	yes
-	-	>10	yes

thickness is defined to be embrittled independent of the values for beta phase thickness and hydrogen concentration. Cladding with a hydrogen concentration greater than 10 at.% is defined to be embrittled independent of the value of beta phase thickness or oxide layer thickness.

Embrittled cladding will be assumed to crack when it is cooled at the temperature of 820 K at a rate greater than 50 K/s. The temperature of 820 K is based upon the Zr-H phase diagram and experimental results. As shown previously in Figure 4, a phase change occurs in the Zr-H system for a broad range of hydrogen concentrations at a temperature of about 820 K. As shown in Figure 7 for an experiment

Figure 7. Temperature history and corresponding hydrogen release.

performed for the QUENCH program at FZK, a significant release in absorbed hydrogen was observed to occur as cladding cooled to a temperature less than 800 K.⁷ The cooling rate of 50 K/s is based upon the cooling rate used in experiments that showed cracking of the cladding during quenching.

Ideally, a calculation would be performed of the stresses and strains in the metallic and oxidic layers of the cladding due to the large radial temperature gradients which occur during the quenching of hot fuel rods. The calculated stresses and strains would be compared with a model that defined the stresses and strains for cracking of the cladding as a function of temperature and concentrations of hydrogen and oxygen. The application of these models would account for the reduction in ductility of the cladding that occurs in certain phases of the Zr-O and Zr-H phase diagrams. But models to calculate these stresses and strains in the cladding require structural material properties as a function of concentrations of hydrogen and oxygen that are not available for high temperatures. So a determination of the times and localities at which the cladding cracks can only be based upon experimental results.

As shown previously in Figure 7, the cracking of the cladding during quenching results in release of the hydrogen absorbed in the metallic phase of the cladding. This release of hydrogen will be modeled by applying the same simplified approach used in modeling hydrogen uptake after complete dissolution of the oxide layer. This simplified approach was presented in Section 3 and is justified by experimental results that show hydrogen is quickly released following a change in boundary conditions that allows the release of hydrogen.⁴ After cracking of the oxide layer occurs, the oxide layer will be assumed to apply no resistance to the diffusion of hydrogen from the metallic layer to the bulk coolant. The rate of hydrogen release will be based on experimental results shown in Figure 7. This figure shows that hydrogen was released during a 20 s period after the cladding cooled to a temperature less than 800 K.

The rate of hydrogen release will be calculated by the equation

$$C_H = C_{HS} \left(1 - \left[\frac{(t - t_{crk})}{t_{req}} \right] \right) \quad (48)$$

where

C_H	=	fractional hydrogen concentration at time t (H/Zr ratio),
C_{HS}	=	fractional hydrogen concentration just before start of cracking of cladding (H/Zr ratio),
t	=	time (s),
t_{crk}	=	time at which cladding cracked (s),
t_{req}	=	experimentally measured release time (s).

Based upon the experimental results shown in Figure 7, the variable t_{req} in the above equation is assigned a value of 20 s.

The release of hydrogen to the bulk coolant during a time step is given by the equation

$$w_{hrci} = 2\pi r_o \Delta z \xi (C_{H1} - C_{H2}) \rho_m \quad (49)$$

where

w_{hrci}	=	kg-mol of H_2 released to bulk coolant due to cracking of cladding at axial node i ,
r_o	=	outer node of cladding at axial node i (m),
Δz	=	height of axial node i (m),
ξ	=	thickness of metallic phase of cladding at axial node i (m),
C_{H1}	=	fractional hydrogen concentration at start of time step (H/Zr ratio),
C_{H2}	=	fractional hydrogen concentration at end of time step (H/Zr ratio),
ρ_m	=	molar density of Zr in Zircaloy (70.5 kg-mol/m ³).

Hydrogen release is also caused by the oxidation of cladding.⁴ This mechanism for release occurs because the hydrogen solubility in ZrO_2 is very small. In this sense, hydrogen behaves similar to the fission product tellurium, which is strongly bound by Zr but not by ZrO_2 .⁴ With respect to tellurium, oxidation "squeezes" the tellurium into the ever diminishing metallic part of the cladding and then a puff of tellurium release occurs as the last small part of the metallic layer is oxidized. Since the concentration of tellurium in the cladding is estimated to be much less than the concentration of hydrogen, oxidation of the cladding will not be considered to squeeze the hydrogen into the ever diminishing metallic layer. Instead, an immediate release of the hydrogen in the portion of the cladding oxidized during a time step will be assumed. The oxidation driven release of hydrogen will be calculated by the equation

$$w_{hroi} = 2\pi r_o \Delta z (\xi_1 - \xi_2) C_H \rho_m \quad (50)$$

where

w_{hroi}	=	kg-mol of hydrogen released to bulk coolant at axial node i,
r_o	=	outer radius of cladding at axial node i (m),
Δz	=	height of axial node i (m),
ξ_1	=	thickness of metallic layer of cladding at axial node i at start of time step (m),
ξ_2	=	thickness of metallic layer of cladding at axial node i at end of time s,
C_H	=	fractional hydrogen concentration at start of time step at axial node i (H/Zr ratio),
ρ_m	=	molar density of Zr in Zircaloy (70.5 kg-mol/m ³).

5. Implementation of Zr-H Interaction Models

The modeling of hydrogen uptake and its consequences requires the implementation of several different models into different parts of SCDAP/RELAP5. This section defines where in the SCDAP/RELAP5 framework the different models are to be linked.

Five subroutines need to be programmed to calculate the five individual models defined in this report for Zr-H interaction; (1) OXDIF to calculate the diffusion of oxygen from the bulk gas into the cladding and to calculate the possible dissolution of the oxide layer, (2) H2UPTK to calculate the uptake of hydrogen in the cladding following the dissolution of the oxide layer in a steam-starved region, (3) EMBRTL to determine whether the cladding has been embrittled by oxidation and hydrogen uptake, (4) CLDCRK to calculate the time at which the cladding cracks at any location and thus paths are created for the release of hydrogen from the cladding to the bulk fluid, and (5) H2REL to calculate the rate of release of hydrogen from the cladding to the bulk fluid. These five subroutines will be connected to the existing SCDAP/RELAP5 programming framework as shown in Figure 8. In this figure, the solid lines and solid

Figure 8. Implementation of Zr-H interaction models into frame work of SCDAP/RELAP5 programming.

boxes represent connections and subroutines that currently exist and the dashed lines and dashed boxes represent connections and subroutines to be added to model Zr-H interaction and its consequences. Subroutine FUELAN is the driver subroutine for calculating the behavior of fuel rods. It calls subroutines such as LIQSOL that calculates the meltdown of fuel rods and OXIDIZ that calculates the oxidation of fuel rod cladding. Two subroutines need to be programmed for MATPRO to calculate the oxygen transport material properties of the cladding. A subroutine named DIFZOX will be programmed to calculate the diffusion coefficient of oxygen in the oxide layer as a function of temperature. A subroutine named

DIFZMT will be programmed to calculate the diffusion coefficient of oxygen in the cladding metallic layer as a function of temperature.

An input option will be implemented to compare oxygen uptake and resulting fuel rod heatup as calculated using the existing OXSTAT subroutine with the oxygen uptake and resulting heat generation as calculated using subroutine OXDIF. These subroutines use different methods to calculate oxygen uptake. Subroutine OXSTAT uses the parabolic kinetics method and subroutine OXDIF uses the integral diffusion method. The integral diffusion method is considered to be more accurate under conditions of steam starvation and transient temperatures but has not been assessed using the results of integral severe fuel damage tests. On the other hand, the parabolic kinetics method has been thoroughly assessed using the results of integral fuel rod tests and assessment results indicate that it is generally adequate for severe accident analysis. If the comparisons of calculated and measured heatup as calculated by the OXDIF model are as good or better than those using the OXSTAT model, then the OXDIF model will be made the default model for calculating oxygen uptake and the resulting heat generation.

6. Testing and Assessment of Zr-H Interaction Models

The modeling improvements described in Sections 2 through 4 will be assessed using the results of four integral severe fuel damage experiments and with a calculation of a TMLB' accident in a PWR. The test matrix for assessment is defined in Table 5. The PBF SFD 1-4¹² and KfK CORA-13¹³ test problems

Table 5. Matrix of test problems for assessing models for Zr-H interaction and its consequences

Problem No.	Problem name	Areas of calculation where improvements are expected
1	PBF SFD 1-4	1. Decrease from 0.86 to 0.22 the fraction of oxidation at 0.85 m elevation, which is a location with steam starvation for a period of time
2	KfK CORA-13	1. Decrease from 0.40 to <0.05 the fraction of cladding oxidation in the 0.80 to 1.0 m interval of elevation 2. hydrogen uptake and subsequent release during heatup phase of experiment
3	FZK QUENCH #03077_2	1. Release of absorbed hydrogen during quenching phase of experiment
4	PBF SFD-ST	1. No improvement required but verification needed that modeling also performs correctly in steam-rich environment
5	Surry TMLB'	1. No areas for improvement are identified but useful to evaluate impact of Zr-H models on a full-plant analysis

will exercise the oxygen diffusion model and the modeling of the dissolution of the oxide layer into the metallic layer in the upper part of the test bundles where steam-starved conditions existed for a period of time. The KfK CORA-13 test had a measurement of the transient mass flow rate of hydrogen out of the test bundle region and thus will allow assessment of the modeling of hydrogen absorption after dissolution of the oxide layer and the subsequent release of the hydrogen as the cladding continues to heatup. The FZK QUENCH 03077_2 test⁷ will assess the capability of the models to calculate the embrittlement of cladding due to hydrogen uptake and the release of hydrogen after cracking of embrittled fuel rods during quenching. The PBF SFD-ST test¹⁴ will be used to verify that the Zr-H interaction models have not adversely effected calculations for steam-rich environments in which minimal Zr-H interactions are expected. The Surry TMLB' problem¹⁵ will be calculated to evaluate the effect of the Zr-H models on the behavior calculated for a severe accident in a full-plant.

7. Summary

Preliminary designs were described for models of the interaction of Zircaloy and hydrogen and the consequences of this interaction on the behavior of fuel rod cladding during severe accidents. The modeling of this interaction and its consequences involves the modeling of seven processes; (1) diffusion of oxygen from the bulk gas to the boundary layer at the external cladding surface, (2) diffusion from the boundary layer into the oxide layer at the cladding external surface, (3) diffusion from the inner surface of the oxide layer into the metallic part of the cladding, (4) uptake of hydrogen in the event that the cladding oxide layer is dissolved in a steam-starved region, (5) embrittlement of cladding due to hydrogen uptake, (6) cracking of cladding during quenching due to its embrittlement and (7) release of hydrogen from the cladding after cracking of the cladding. An integral diffusion method is described for calculating the diffusion processes in the cladding. The boundary conditions applied for the calculation of the diffusion of oxygen into the cladding are; (1) mass flux of oxygen into the external surface of the oxide layer equals the mass flux of oxygen into boundary layer at the external surface of the cladding, (2) oxygen to zirconium atomic ratio at the external surface of the oxide layer defined by the phase diagram for the Zr-O system, (3) oxygen to zirconium atomic ratio at the inner surface of the oxide layer defined by the Zr-O phase diagram, (4) oxygen to zirconium atomic ratio at the external surface of the metallic layer defined by the Zr-O phase diagram (terminal solubility), (5) mass flux of oxygen at outer surface of metallic layer equal to mass flux of oxygen at inner surface of oxide layer, and (6) zero mass flux of oxygen at the inner surface of cladding. Experimental and theoretical results were presented that showed the uptake of hydrogen in the event of dissolution of the oxide layer occurs rapidly and that showed the release of hydrogen in the event of cracking of the cladding occurs rapidly. These experimental results were used as a basis for calculating the rate of hydrogen uptake and the rate of hydrogen release. The uptake of hydrogen is limited to the equilibrium solubility calculated by applying Sievert's law. The uptake of hydrogen is an exothermic reaction that accelerates the heatup of a fuel rod. An embrittlement criteria was described that accounts for hydrogen and oxygen concentration and the extent of oxidation. A design was described for implementing the models for Zr-H interaction into the programming framework of the SCDAP/RELAP5 code. An input option was proposed that provides the capability to compare the accuracy of the integral diffusion and parabolic kinetics methods for calculating cladding oxidation and resulting heat generation. A test matrix was described for assessing the impact of the Zr-H interaction models on the calculated behavior of fuel rods in severe accident conditions.

8. References

1. The SCDAP/RELAP5 Development Team, "SCDAP/RELAP5/MOD3.2 Code Manual, Volume II: Damage Progression Model Theory," NUREG/CR-6150, INEL-96/0422, Revision 1, October 1997.
2. D. R. Olander, "Materials chemistry and transport modeling for severe accident analyses in light-water reactors, I: External cladding oxidation," Nuclear Engineering and Design 148 (1994), pages 253-271.
3. D. R. Olander, "Materials chemistry and transport modeling for severe accident analyses in light-water reactors II: Gap processes and heat release," Nuclear Engineering and Design 148 (1994), pages 273-292.
4. M. Moalem and D. R. Olander, "Oxidation of Zircaloy by steam," Journal of Nuclear Materials 182 (1991), pages 170-194.
5. M. Steinbruck et al., "Investigations of H₂ absorption of Zircaloy-4 at high temperatures," Third International QUENCH Workshop, Karlsruhe, Germany, December 2 - 4, 1997.
6. H. Chung and G. Thomas, "Zircaloy-Oxidation and Hydrogen-Generation Rates in Degraded-Core Accident Situations," CONF-821026-13, International Workshop on the Impact of Hydrogen on Water Reactor Safety, Albuquerque, NM, Oct. 3, 1982.
7. P. Hofmann et al., "Experiments on the Quench Behavior of LWR Fuel Rod Segments," Third International QUENCH Workshop, Karlsruhe, Germany, December 2 - 4, 1997.
8. T. Furuta, H. Uetsuka, and S. Kawasaki, "Estimation of Conservatism of Present Embrittlement Criteria for Zircaloy Fuel Cladding Under LOCA," Zirconium in the Nuclear Industry, Sixth International Symposium, ASTM STP 824, D. G. Franklin and R. B. Adamson, Eds., American Society for Testing and Materials, 1984, pages 734-746.
9. Appendix K, "ECCS Evaluation Models," 10 CFR Part 50.46.
10. H. M. Chung and T. F. Kassner, "Embrittlement Criteria for Zircaloy Fuel Cladding Applicable to Accident Situations in Light-Water Reactors: Summary Report," NUREG/CR-1344, ANL-79-48, January 1980.
11. S. L. Seiffert, "Effect of Hydrogen on the Oxygen Embrittlement of Beta-Quenched Zircaloy-4 Fuel Cladding," Zirconium in the Nuclear Industry: Fifth Conference, ASTM STP 754, D. G. Franklin, Ed., American Society for Testing and Materials, 1982, pages 302-328.
12. D. A. Petti et al., "Power Burst Facility (PBF) Severe Fuel Damage Test 1-4 Test Results Report," NUREG/CR-5163, EGG-2542, April, 1989.
13. S. Hagen et al., "Results of SFD Experiment CORA-13 (OECD International Standard Problem 31)," KfK 5054, February 1993.
14. Alan D. Knipe et al., "PBF Severe Fuel Damage Scoping Test, Test Results Report," NUREG/CR-4683, EGG-2413, August 1986.
15. The SCDAP/RELAP5 Development Team, "SCDAP/RELAP5/MOD3.2 Code Manual Volume V: Developmental Assessment" NUREG/CR-6150, INEL-96/0422, Revision 1, October 1997.

Appendix A

Oxygen Transport Material Properties

A correlation for the coefficient of diffusion of oxygen in the oxide layer^{A1-1} for oxide layer temperatures less than 1773 K is;

$$D_{ox} = 75.0 \times 10^{-4} \exp(-22600/T) \quad (A-1)$$

where

D_{ox} = diffusion coefficient of oxygen in oxide layer (m^2/s),

T = temperature of oxide layer (K).

Equation (A-1) is based upon constants for modeling of oxidation by parabolic kinetics, which in turn are based upon data obtained from experiments on the oxidation of Zircaloy cladding.

For an oxide layer temperature greater than 1773 K, a correlation for the coefficient of diffusion of oxygen in the oxide layer^{A1-1} is

$$D_{ox} = 20 \times 10^{-4} \exp(-24000/T). \quad (A-2)$$

A correlation^{A1-1} for the coefficient of diffusion of oxygen in the metallic layer of the cladding is:

$$D_M = 4.1 \times 10^{-4} \exp(-25700/T). \quad (1-1)$$

An alternative set of correlations for oxygen diffusion coefficients is provided in Reference A1-2. According to this reference, for the temperature range of 1273 K to 1798 K, the correlations for oxygen diffusion coefficients are:

$$D_{ox} = 8.67 \times 10^{-4} \exp(-40495/RT) \quad (1-1)$$

$$D_{\alpha M} = 1.54 \times 10^{-4} \exp(-48020/RT) \quad (1-1)$$

$$D_{\beta M} = 0.263 \times 10^{-5} \exp(-28200/RT) \quad (1-1)$$

Appendix A1

where

$D_{\alpha M}$ = oxygen diffusion coefficient in alpha phase of cladding (m^2/s).

$D_{\beta M}$ = oxygen diffusion coefficient in beta phase of cladding (m^2/s).

R = $1.987 \text{ cal/mole} \cdot \text{K}$.

For temperature in the range of $1798 \leq T \leq 2098 \text{ K}$, D_{ox} is given the correlation

$$D_{\text{ox}} = 0.47 \times 10^{-5} \exp(-25803/RT), \quad (1-1)$$

A correlation^{A1-1} for the binary diffusivity is

$$D_g = \frac{1.03 \times 10^{-4}}{p_{\text{tot}}} \left(\frac{T}{1273} \right)^{1.68} \quad (1-1)$$

where

T = temperature of bulk gas (K).

p_{tot} = bulk pressure (MPa).

A1. References

- A1-1. D. R. Olander, "Materials chemistry and transport modeling for severe accident analyses in light-water reactors, I: External cladding oxidation," Nuclear Engineering and Design 148 (1994), pages 253-271.
- A1-2. A. V. Berdyshev, L. V. Matveev, and M. S. Veshchunov, "Development of the Data Base for the Kinetic Model of the Zircaloy 4/Steam Oxidation at High Temperature ($1000^{\circ}\text{C} \leq T \leq 1825^{\circ}\text{C}$)."
- IBRAE-97-05, Russian Academy of Sciences, Nuclear Safety Institute, March 1997.