CONF-970834--12

INTERFACIAL SEGREGATION IN OXIDE SCALES ON NiCrAl-BASED ALLOYS

K. Prüßner, K. B. Alexander, B. A. Pint, P. F. Tortorelli and I. G. Wright

Metals & Ceramics Division, Oak Ridge National Laboratory, P.O. Box 2008, Oak Ridge, TN 37831

Previous studies addressing the segregation of reactive elements in protective oxide scales and their beneficial effect on scale adhesion have primarily concentrated on primary alumina-formers (e.g. β -NiAl and FeCrAl).¹ In our study the isothermal oxidation behaviour of three NiCrAl alloys, which form complex oxide scales^{2,3} was studied in air at 1473 K for 100 hrs.. The composition (in at.-%) of these alloys is the following: General Electric alloy **René N5** (64.9 Ni, 7.8 Cr, 13.9 Al, 0.1 Fe, 2.1 Ta, 0.05 Hf, 1.6 W, 1.0 Re, 0.15 Si, 7.3 Co, 0.9 Mo, 0.003 Y, 0.003 Zr, 4 ppm S, 0.25 C), **Ni-7Cr-6.5Al+Y** (80.1 Ni, 7.2 Cr, 12.5 Al, 0.01 Fe, 0.14 Si, 0.012 Y, 18 ppm S, 0.05 C) and **Ni-10Cr-10Al+Y** (71.2 Ni, 9.9 Cr, 18.8 Al, 0.01 Fe, 0.02 Si, 0.041 Y, 16 ppm S, 0.04 C).

The resulting oxide scales were characterized by scanning electron microscopy (SEM) and cross-sectional transmission electron microscopy (TEM) techniques. Segregation at internal interfaces was analyzed in the STEM mode on a Philips CM200 FEG-TEM, operated at 200 kV and equipped with a Link ultrathin-window EDS detector. The probe size of the electron beam was about 1.5 nm. Spectra were recorded with grain boundaries oriented parallel to the electron beam.

The oxide scale on René N5 (~5 μ m) consists of columnar α -Al₂O₃ at the bottom (~4 μ m) and a mixed layer of spinel (Ni, Co, Ta) (Al,Cr)₂O₄ and α -Al₂O₃ (~1 μ m) at the top (Fig. 1a, 2a). The mixed spinel/alumina layer contains numerous precipitates of Ta,Y,Cr(Hf,Re)-oxides. These are concentrated at the interface between the columnar alumina and the mixed layer. This mixed layer of the scale is prone to spallation. Similar oxide particles can also be found on the scale surface. Spallation of the complete scale exposing the bare alloy occurs only around particles in the alloy, which consist of Ta,Y,Cr(Hf,Re)-oxide in the center, surrounded by spinel (Ni, Co, Ta) (Al,Cr)₂O₄ and α -Al₂O₃. Segregation of Ta and Y at oxide grain boundaries, both in the alumina and in the spinel, was found (Fig. 3a). Some oxide grain boundaries also exhibited segregation of Hf and Re.

On Ni-7Cr-6.5Al+Y, the scale (~9 μ m) consists mainly of columnar Cr-doped α -Al₂O₃ (Fig. 1b, 2b). On top of it is a thin, porous mixed layer of equiaxed spinel (NiAl₂O₄) and α -Al₂O₃, as well as some NiO. Over time NiO transforms to NiAl₂O₄ and NiAl₂O₄ eventually to α -Al₂O₃; both transformations are pseudomorphic. Spallation of the scale occurred only in a few areas associated with the formation of Y₂O₃, Y₃Al₅O₁₂ (garnet) and α -Al₂O₃ at Y-rich alloy grain boundaries. Y-rich oxide particles can be found on the scale surface. Yttrium was also found to be segregated at oxide grain boundaries (Fig. 3b) and at the scale/metal interface.

Ni-10Cr-10Al+Y forms an oxide scale (~8 μ m) that consists mainly of columnar Cr-doped α -Al₂O₃ (Fig. 1c). Y-rich oxide particles can be found on the scale surface. The higher level of Y in this alloy results in the formation of Y-rich precipitates at all alloy grain boundaries. Preferential internal oxidation ultimately leads to the formation of Y₂O₃, Y₃Al₅O₁₂ (garnet) and α -Al₂O₃ at these grain boundaries. Due to the volume change associated with the formation of these phases, almost complete spallation of the oxide scale is initiated from here.

The results are consistent with previous results on primary alumina-formers. Reactive elements present in the alloy diffuse into the oxide scale and segregate to grain boundaries where they change the diffusion processes resulting in a columnar grain structure of the alumina scale.⁴

References:

- 1) B. A. Pint, *Oxid. Met.* 45 (1996) 1.
- 2) C. S. Giggins, F. S. Pettit, *J. Electrochem. Soc.* 118 (1971) 1782.
- 3) A. Kumar, M. Nasrallah, D. L. Douglass, *Ox. Met.* 8 (1974) 227.
- 4) Research at the Oak Ridge National Laboratory (ORNL) SHaRE User Facility was sponsored by the Division of Materials Sciences, U.S. Department of Energy, under contract DE-AC05-96OR22 464 with Lockheed Martin Energy Research Corp., and by an appointment (KP) to the ORNL Postdoctoral Research Associates Program, which is administered jointly by the Oak Ridge Institute for Science and Education and ORNL.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

"The submitted manuscript has been authored by a contractor of the U.S. Government under contract No. DE-AC05-96OR22464. Accordingly, the U.S. Government retains a nonexclusive, royalty-free licence to publish or reproduce the published form of this contribution, or allow others to do so, for U.S. Government purposes."

MASTER

FIG. 1: SEM backscattered electron (BSE) images of polished and fractured cross sections.
 FIG. 2: STEM annular dark field image of cross sections through the oxide scale.
 FIG. 3: EDS spectra showing segregation of Ta and Y at alumina grain boundaries.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.