89800

RECEIVED

AUG 04 1997

OSTI

**Crystal structure of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ by neutron
powder diffraction analysis***

ANL/IPNS/PP--89800

Yasushi Idemoto, ^{a,b} James W. Richardson, Jr., ^a Nobuyuki Koura, ^b

Shinji Kohara, ^b and C.-K. Loong ^a

^a Intense Pulsed Neutron Source, Argonne National Laboratory, Argonne, Illinois 60439-4814, U. S. A.

^b Department of Industrial Chemistry, Faculty of Science and Technology, Science University of Tokyo, 2641 Yamazaki, Noda-shi, Chiba 278, Japan

The submitted manuscript has been authored by a contractor of the U. S. Government under contract No. W-31-109-ENG-38. Accordingly, the U. S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U. S. Government purposes.

Submitted to Journal of The Electrochemical Society

MASTER

*Work supported by U. S. Department of Energy, BES, contract No. W-31-109-ENG-38

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

The submitted manuscript has been authored by a contractor of the U. S. Government under contract No. W-31-109-ENG-38. Accordingly, the U. S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U. S. Government purposes.

ng

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Crystal structure of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ by neutron powder diffraction analysis

Yasushi Idemoto, ^{a,b} James W. Richardson, Jr., ^a Nobuyuki Koura, ^b

Shinji Kohara, ^b and C.-K. Loong ^a

^a Intense Pulsed Neutron Source, Argonne National Laboratory, Argonne, Illinois 60439-4814, U. S. A.

^b Department of Industrial Chemistry, Faculty of Science and Technology, Science University of Tokyo, 2641 Yamazaki, Noda-shi, Chiba 278, Japan

ABSTRACT

The crystal structure of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ was determined by neutron powder diffraction. A final weighted R-factor of 4.54% was obtained for the refinement of 2373 reflections by the Rietveld method from a sample synthesized using $^7\text{Li}_2\text{CO}_3$ and K_2CO_3 (99.9% pure). Slight distortion of the CO_3^{2-} units in the monoclinic cell was observed; the O(1)-C-O(2) angle and C-O(3) length are larger than those for the other C-O bonds and O-C-O angles. These local-structure characteristics can be explained by the difference in the ionic size of Li^+ and K^+ , and the different electrostatic interactions between the cations and CO_3^{2-} units.

Introduction

The promising efficiency and attractive environmental features of molten carbonate fuel cells have attracted keen attention from electrochemists in recent years. In particular, concerns such as corrosion of electrodes and reduction processes of oxygen in mixed Li_2CO_3 - K_2CO_3 molten salts have been the subject of intense studies. Both issues involve electroactive CO_3^{2-} species, their interaction with cations of the electrodes and inter-diffusion with O_2 and CO_2 . These properties are closely related to the structural differences of the materials near and in between the eutectic compositions. Information regarding the configuration of CO_3^{2-} with respect to the alkali ions in molten and solid-state solution of Li_2CO_3 - K_2CO_3 is not complete. Recent molecular-dynamics (MD) simulations of molten $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ indicated that a Li^+ ion is located near one O atom of a CO_3^{2-} ion, and a K^+ ion is at an intermediate position between two O atoms of the CO_3^{2-} ion.¹⁻³ Furthermore, simulations suggested that cation sites surrounding CO_3^{2-} ions change with the Li/K ratio.² However, MD simulations¹⁻³ and *ab initio* calculations⁴ do not determine precisely the near-neighbor distances and angles, nor do they identify geometric changes in CO_3^{2-} unit responding to preferential coordination of Li^+ and K^+ ions. Detailed crystal structure determinations can provide these insights. In particular, structural changes resulting from changes in Li/K ratio may be correlated with variations of thermodynamic properties and performance of the fuel cells. This letter reports the crystal structure of a $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ powder by neutron-diffraction measurements.

Several authors have reported the solid-liquid phase diagram for mixtures of Li_2CO_3 and K_2CO_3 .^{5,6} These data suggest that a solid solution with composition $\text{Li}_2\text{CO}_3\text{:K}_2\text{CO}_3 = 0.5\text{:}0.5$ may form a single-phase material at room temperature. The crystal structure of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ has been studied by x-ray diffraction⁷ and the lattice parameters and space group were reported. However, a detailed crystal structure determination was not achieved. To the best of our knowledge, no neutron-diffraction studies of Li_2CO_3 - K_2CO_3 have been reported so far. This may be in part due to difficulties encountered when analyzing neutron-diffraction data from samples containing natural Li (^6Li 7.42% + ^7Li 92.58%), since the neutron absorption coefficient

of ^6Li is large. The samples used in this study were prepared by mixing $^7\text{Li}_2\text{CO}_3$ with K_2CO_3 to avoid this problem.

Experimental Details

Li_2CO_3 powder of 99.9% purity and 99.9% ^7Li isotopic substitution, supplied by Tomiyama's High Purity Chemicals, and K_2CO_3 powder of 99.9% purity, supplied by Wako Pure Chemical Ind. Ltd., were used as starting materials. The carbonates were dried at 450°C for 12h in air. Li_2CO_3 and K_2CO_3 were then mixed in a 1:1 molar ratio, and placed in an alumina crucible for melting. The sample was first heated at a rate of $30^\circ\text{C}/\text{min}$ to 650°C and kept for 1h in air. The melt was then quenched to room temperature by pouring it on a copper plate in air. The quenched sample was placed in a dry box under flowing dry nitrogen gas, and ground into a powder. The resulting sample was dried at 450°C for 1.5h in air. This process was repeated one time.

Time-of-flight (TOF) neutron powder diffraction was performed using the General Purpose Powder Diffractometer (GPPD) at Argonne's Intense Pulsed Neutron Source (IPNS).⁸ A powder sample was enclosed in a thin-wall vanadium can (11mm diameter, 50 mm long). Independent TOF data were recorded on eight detector banks positioned at scattering angles ranging from $\pm 15^\circ$ to $\pm 150^\circ$. The back-scattering geometry (at a mean scattering angle of $\pm 148^\circ$) corresponds to the highest resolution ($\Delta d/d = 0.25\%$ where d is the atomic spacing). For the measurement of $(^7\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$, a 3.3g of powder was used, and data were collected for 9h at room temperature. The crystal structure was refined with the Rietveld technique (GSAS program⁹).

Results and Discussion

The intensity profile of the $(^7\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ sample was analyzed over a large d -spacing range from 0.5 to 2.9 Å, which consisted of 4910 data points and 2373 reflections. An initial refinement was carried out by assuming a monoclinic unit cell isostructural with K_2CO_3 .⁷ Subsequent analyses concluded a single-phase structure for $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ of monoclinic symmetry (space group $\text{P}2_1/\text{c}$). The final refined parameters are listed in Tables 1 and 2, and the

unit cell is shown in Fig. 1. Fig. 2 illustrates the resulted profile fit where good agreement between the observed and calculated patterns and a low R-factor ($R_{wp} = 4.54\%$) were obtained. The lattice parameters agree reasonably well with those obtained by Christmann and coworkers⁷ previously from x-ray diffraction. As shown in Table 2, our results show that Li^+ and K^+ ions occupy different sites and that all cation sites are fully occupied, in good agreement with previous MD simulations.¹

Selected bond lengths and angles from structural parameters are listed in Table 3. In contrast with the carbonate groups in isostructural K_2CO_3 ,¹⁰ the CO_3 units in $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ are slightly distorted. The $\text{O}(1)\text{-C-O}(2)$ bond angle of $123.2 \pm 0.2^\circ$ is somewhat larger than that ($118.4 \pm 0.3^\circ$) of $\text{O}(2)\text{-C-O}(3)$ and $\text{O}(3)\text{-C-O}(1)$. In addition, a longer bond length of $\text{C-O}(3)$ ($1.301 \text{ \AA}$) compared to those of $\text{C-O}(1)$ and $\text{C-O}(2)$ (1.281 and $1.271 \text{ \AA}$, respectively) was clearly identified. A selected portion of the crystal structure is shown in Fig. 3 to illustrate this situation. The 7 atoms shown are located roughly in the plane of the figure. The observed differences in bond distances and angles within the CO_3 unit can be understood by comparing with K_2CO_3 where Li sites would be occupied by K atoms. While this group of atoms in K_2CO_3 closely follows a D_{3h} point symmetry around carbon, in $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ the local symmetry is closer to C_{2v} . Furthermore, each Li^+ ion is 4-fold coordinated whereas K^+ exhibits 7-fold coordination. Because Li^+ is considerably smaller than K^+ , these differences in local symmetry and coordination will strongly influence the bond lengths and angles. Local structural variations in $(\text{Li}_x\text{K}_{1-x})_2\text{CO}_3$ materials can, therefore, be explained by the difference in ionic size between Li^+ and K^+ and the consequent differences in electrostatic interactions.

A separate sample of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ was prepared, in the same manner as the first sample, using natural Li_2CO_3 . As expected, a Rietveld refinement of the diffraction data from this sample resulted in a larger R_{wp} (5.28%) than that obtained with the ^7Li enriched sample (4.54%). The improvement from ^7Li enrichment is due to the lower absorption coefficient of ^7Li than ^6Li . Complete details of neutron-diffraction results for both the isotopic and natural Li_2CO_3 , K_2CO_3 , $(\text{Li}_{0.43}\text{K}_{0.57})_2\text{CO}_3$, and $(\text{Li}_{0.62}\text{K}_{0.38})_2\text{CO}_3$ samples will be reported in a separate paper.

Conclusion

The crystal structure of $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ has been determined by TOF neutron powder diffraction. Asymmetry in the CO_3^{2-} units in terms of larger O(1)-C-O(2) bond angle and C-O(3) bond length than the other corresponding angles and lengths in the CO_3^{2-} unit was observed. Differences in bond angles and bond lengths are influenced by electrostatic interactions between the CO_3^{2-} units and the Li^+ ion and K^+ ions. The improved refinements - R_{wp} from 5.28% to 4.54% - by using isotopically enriched samples, prepared by using $^7\text{Li}_2\text{CO}_3$ instead of the natural compound, demonstrates that ^7Li isotopic substitution is effective for the determination of an accurate crystal structure by neutron diffraction.

Acknowledgments

The authors wish to acknowledge the valuable assistance of Ray Thomas (Argonne) in the neutron-diffraction experiments. This work has benefited from the use of the Intense Pulsed Neutron Source at Argonne National Laboratory. This facility is funded by the U.S. Department of Energy, BES-Materials Science, under CONTRACT W-31-109-ENG-38.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

References

1. N. Fujimoto and N. Koura, *Denki Kagaku*, **57**, 910 (1989).
2. N. Fujimoto and N. Koura, *Denki Kagaku*, **59**, 594 (1991).
3. J. T. W. M. Tissen, G. J. M. Janssen and J. P. van der Eerden, *Mol. Phys.*, **82**, 101 (1994).
4. N. Koura, S. Kohara, K. Takeuchi, S. Takahashi, M.-L. Saboungi, L. A. Curtiss and M. Grimsditch, *J. Mol. Structure*, in press.
5. G. J. Janz and M. Lorenz, *J. Chem. Eng. Data*, **6**, 321 (1961).
6. K. Babcock and J. Winnic, *J. Chem. Eng. Data*, **33**, 96 (1988).
7. M. Christmann, N. Sandeghi and G. Papin, *Rev. Chim. Miner.*, **15**, 312 (1978).
8. J. D. Jorgensen, J. Faber Jr., J. M. Carpenter, R. K. Crawford, J. R. Haumann, R. L. Hitterman, R. Kleb, G. E. Ostrowski, F. J. Rotella and T. G. Worlton, *J. Appl. Cryst.* **22**, 321 (1989).
9. A. C. Larson and R. B. von Dreele, Los Alamos National Laboratory Report, No. LA-UR 86-748, (1987).
10. B. M. Gatehouse and D. J. Lloyd, *J. Chem. Soc., Dalton*, 70 (1973).

Figure Captions

Figure 1. The crystal structure (space group $P2_1/c$) of $(Li_{0.5}K_{0.5})_2CO_3$. The unit cell is shown by the parallelepiped.

Figure 2. Neutron powder diffraction data and Rietveld refinement profile fit for monoclinic $(Li_{0.5}K_{0.5})_2CO_3$. The symbols (+) represent the background-subtracted data. The solid line is the calculated profile. Tick marks below the profile mark the positions of allowed Bragg reflections. The differences between the observed and calculated intensities are shown at the bottom.

Figure 3. A selected portion of crystal structure for $(Li_{0.5}K_{0.5})_2CO_3$, illustrating the coordination of Li^+ and K^+ ions with the CO_3^{2-} units. Atoms are labeled according to the scheme given in Table 3.

Table 1 The lattice parameters and cell volume for $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ at room temperature.

Numbers within parentheses are statistical standard deviations of the last significant digit.

	Neutron	x-ray ⁷
a (Å)	7.22284(7)	7.232(5)
b (Å)	7.07673(8)	7.080(4)
c (Å)	7.59397(9)	7.619(5)
β	127.421(1)	127.5(1)
V (Å ³)	308.272(3)	

Table 2 The crystal structural parameters for $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$ at room temperature. Rietveld refinements were based on a monoclinic structure (space group $\text{P2}_1/\text{c}$), see Table 1. The occupation factors of all atoms were fixed to unity. The weighted R-factors was 4.54%.

Atom	Site	x	y	z	$U_{11}(\text{\AA}^2)$	$U_{22}(\text{\AA}^2)$	$U_{33}(\text{\AA}^2)$	$U_{12}(\text{\AA}^2)$	$U_{13}(\text{\AA}^2)$	$U_{23}(\text{\AA}^2)$
Li	4e	0.4004(9)	0.0676(8)	0.1019(9)	0.0234(28)	0.0355(32)	0.0383(34)	0.0068(22)	0.0275(28)	0.0025(25)
K	4e	-0.1716(5)	0.3553(4)	0.1685(5)	0.0224(17)	0.0220(18)	0.0447(23)	-0.0011(11)	0.0234(17)	0.0023(13)
C	4e	0.2939(3)	0.3326(2)	0.2132(3)	0.0206(8)	0.0189(8)	0.0254(10)	-0.0023(8)	0.0165(8)	-0.0039(8)
O(1)	4e	0.7436(3)	-0.0243(2)	0.2092(3)	0.0296(11)	0.0193(11)	0.0310(12)	0.0030(8)	0.0240(10)	0.0075(9)
O(2)	4e	0.1596(3)	0.1899(3)	0.1294(3)	0.0301(11)	0.0168(10)	0.0421(14)	-0.0032(9)	0.0277(11)	-0.0026(9)
O(3)	4e	0.4787(3)	0.3328(3)	0.2207(4)	0.0285(11)	0.0287(10)	0.0552(15)	-0.0094(10)	0.0346(11)	-0.0153(11)

Table 3 Selected bond lengths (in Å) and bond angles (in deg.) for $(\text{Li}_{0.5}\text{K}_{0.5})_2\text{CO}_3$.^a

$\text{C}_1\text{-O}(1)_5$	1.281(2)	$\text{O}(1)_5\text{-C}_1\text{-O}(2)_1$	123.2(2)
$\text{C}_1\text{-O}(2)_1$	1.271(2)	$\text{O}(2)_1\text{-C}_1\text{-O}(3)_1$	118.3(2)
$\text{C}_1\text{-O}(3)_1$	1.301(2)	$\text{O}(3)_1\text{-C}_1\text{-O}(1)_5$	118.5(2)
$\text{Li}_1\text{-O}(1)_4$	1.942(6)		
$\text{Li}_1\text{-O}(2)_1$	2.065(5)	$\text{Li}_1\text{-C}_1\text{-O}(1)_5$	174.5(2)
$\text{Li}_1\text{-O}(3)_6$	1.977(6)	$\text{Li}_1\text{-C}_1\text{-O}(2)_1$	60.5(2)
$\text{K}_1\text{-O}(1)_5$	2.767(3)	$\text{Li}_1\text{-C}_1\text{-O}(3)_1$	58.0(2)
$\text{K}_1\text{-O}(2)_2$	2.794(4)	$\text{Li}_5\text{-C}_1\text{-O}(2)_1$	170.8 (2)
$\text{K}_1\text{-O}(3)_7$	2.789(3)		
$\text{C}_1\text{-Li}_1$	2.370(5)	$\text{K}_1\text{-C}_1\text{-O}(1)_5$	60. 2(1)
$\text{C}_1\text{-Li}_5$	2.417(5)	$\text{K}_1\text{-C}_1\text{-O}(2)_1$	63.2(1)
$\text{C}_1\text{-K}_1$	3.172(3)	$\text{K}_1\text{-C}_1\text{-O}(3)_1$	175.9(2)
$\text{Li}_1\text{-K}_3$	3.396(6)		
$\text{Li}_1\text{-Li}_4$	2.843(1)	$\text{Li}_1\text{-C}_1\text{-K}_1$	123.7 (2)
$\text{K}_1\text{-K}_3$	4.058(3)		

^aSubscripts indicate the following equivalent positions.

1	x	y	z
2	-x	y+(1/2)	-z+(1/2)
3	-x	y-(1/2)	-z+(1/2)
4	-x+1	-y	-z
5	-x+1	y+(1/2)	-z+(1/2)
6	-x+1	y-(1/2)	-z+(1/2)
7	x-1	y	z

Fig. 1

Fig.2

Fig. 3