Catalytic Conversion of Light Alkanes - Phase V

RECEIVED

AUG 12 1997

OSTI

**Topical Report
February 1993 - October 1994**

Work Performed Under Contract No.: DE-FC21-90MC26029

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880

By
Sun Company, Inc.
P. O. Box 1135
Marcus Hook, Pennsylvania 19061-0835

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

**Portions of this document may be illegible
electronic image products. Images are
produced from the best available original
document.**

Disclaimer

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

	<u>PAGE</u>
1.0 <u>SUMMARY OF PROGRAM INCENTIVES</u>	1
2.0 <u>INTRODUCTION</u>	1
2.1 <u>MISSION STATEMENT</u>	1
2.2 <u>TECHNICAL OBJECTIVE</u>	1
3.0 <u>PROGRAM ELEMENTS</u>	3
4.0 <u>PROGRAM OVERVIEW</u>	3
5.0 <u>TBA PROCESS DEVELOPMENT</u>	3
5.1 <u>SUMMARY OF PROCESS DEVELOPMENT ACTIVITIES</u>	3
5.1.1 TBA Process Research - A One-Step Oxidation of Isobutane to TBA	6
5.1.1.1 Isobutane Oxidation Using a Perhaloporphyrin Catalyst .	6
5.1.1.1.1 Introduction	8
5.1.1.1.2 Data & Experimental Procedures	8
5.1.1.1.3 Results and Discussion	8
5.1.1.1.4 Initial Runs	8
5.1.1.1.5 Addition of a Proprietary Additive	15
5.1.1.1.6 Effects of Catalyst Concentration	15
5.1.1.1.7 Effect of Water	15
5.1.1.1.8 Effect of NaOH	15
5.1.1.1.9 Effect of Added Olefins	20
5.1.1.1.10 Effect of Added Acid	20
5.1.1.1.11 Effect of Solvents	20
5.1.1.1.12 Effect of Catalyst Aging.	20
5.1.1.1.13 Sodium Dithionite Effect	25
5.1.1.2 Isobutane Oxidation Using Fe[PPF ₁₆] as Catalyst	25

TABLE OF CONTENTS

	<u>PAGE</u>
5.1.1.3 Isobutane Oxidation Using $\text{Fe}[\text{PP}(\text{C}_2\text{H}_5)_8](\text{NO}_2)_4$ as Catalyst	25
5.1.1.4 Isobutane Oxidation Using Catalyst SUN-Z'	25
5.1.1.5 Catalyst CAT-X and CAT-X'	44
5.1.2 TBA Process Research - A Two-Step Oxidation of Isobutane to TBA	44
5.1.2.1 Experimental Procedures Composition for t-Butyl- hydroperoxide	48
5.1.2.2 Results & Discussion	48
5.1.2.2.1 Reaction Kinetics	52
5.1.2.2.2 Effect of Co-Solvent on SUNZ'	61
5.1.2.2.3 Effect of Staged Catalyst Addition on SUNZ' ..	71
5.1.2.2.4 Effect of Feed Drying	71
5.1.2.3 Catalyst Cost Projections	71
5.1.2.4 Additional Process Development Activities	77
5.1.2.4.1 Effect of Catalyst Concentration	79
5.1.2.4.2 Effect of Pressure	79
5.1.2.4.3 Effect of Buffer (Potassium Acetate)	79
5.1.2.4.4 Effect of Co-Solvent	83
5.1.2.4.5 Effect of Feed Drying	83
5.1.2.5 Catalyst Development Nitroporphines and Halophthalocyanine	83
5.1.2.6 Effect of Feed Drying with Cat-X	87

1.0 SUMMARY OF PROGRAM INCENTIVES

A complete summary of program incentives are given in the first Quarterly Report (January 1 - March 31, 1993) for the continuing Cooperative Agreement.

2.0 INTRODUCTION

2.1 MISSION STATEMENT

The mission of the work presented in this proposal is to generate novel catalytic technology which will permit the development of a simple, efficient and economical process for the direct conversion of natural gas to liquid transportation fuels. This process should be simple enough to liquify natural gas economically even at a remote reservoir site.

The most costly and energy-intensive step in currently applied commercial technology for the conversion of natural gas to liquid fuels is the steam reforming of the light hydrocarbons to produce synthesis gas. The synthesis gas is then converted to methanol which is passed over a catalyst to produce gasoline. If it were possible to catalytically transform natural gas into a methanol rich-oxidate rapidly and efficiently in a single step using air or O₂ as oxidant, the economics of the process would be dramatically improved. In contrast to the energy-inefficient steam reforming process, a direct "methane-to-methanol" process would be highly exoergic and, if properly carried out, would generate usable energy as steam, electricity or both. For these reasons, we are attempting to develop a process for the direct conversion of natural gas to an environmentally superior, methanol-rich liquid fuel oxygenate.

2.2 TECHNICAL OBJECTIVE

The technical objective of this proposal is to synthesize the first effective, practical molecular catalyst and demonstrate its use for the direct air-oxidation of natural gas to a methanol-rich oxidate which can either be used directly or converted into gasoline via known technology.

The light alkanes found in natural gas - methane, ethane, propane, and the butanes are among the most unreactive of all organic substrates. No effective catalysts are known for the selective partial oxidation of these relatively refractory materials. The development of an efficient catalyst for the smooth and selective oxidation of these light alkanes to alcohols will not only provide a solution to the problem of liquifying natural gas, but will create new opportunities to utilize the relatively inexpensive and abundant light alkanes for the production of a variety of valuable fuel and chemical products.

Figure 2-1 shows the relative ease of activation of C-H bonds in the kinds of light alkanes that make up natural gas. This trend is reflected in the ease of catalytic air oxidation of the hydrocarbons: isobutane > butane > propane > ethane > methane. The conversion of any major gas component as

FIGURE 2-1

Hydrocarbon Reactivity Series

well as the entire gaseous mixture to an alcohol-rich oxidate has value both to the gas producer and the liquid transportation fuel producer alike. We are currently capable of oxidizing isobutane well and anticipated being ready for proof-of-concept of a propane to IPA process in the near future. Ethane and methane oxidation will require more time than this. Thus it is proposed that the proof-of-concept stage proceed in several discrete stages: isobutane to TBA, propane to IPA, (ethane to ethanol - optional), and finally methane to methanol. Concurrent with the developmental aspects of each of these phases will be research phases geared to enable us to produce catalysts active enough for each succeeding phase.

3.0 PROGRAM ELEMENTS

Program elements are set forth in the first Quarterly Report of the Cooperative Agreement (January 1 - March 31, 1993).

4.0 PROGRAM OVERVIEW

Phase V, proof of concept for a process to convert isobutane to tert-butyl alcohol, TBA, is the subject of this report.

5.0 TBA PROCESS DEVELOPMENT

We have terminated this program in the midst of a two year developmental proof-of-concept program for the first light alkane to liquid fuel process - the production of a fuel oxygenate from field butanes. There are several ways to accomplish the conversion of field butanes to fuel oxygenates, Scheme 1. This section details advances in the area of development of a process for the conversion of isobutane to tert-butyl alcohol, TBA. During the first year of the proof of concept period established criteria for economically attractive conceptual processes for the production of TBA directly from isobutane (Sun Oxcat-1, Scheme 1), and in a two step process via TBHP (Sun Oxcat-2, Scheme 1). We have now met all of the criteria for Sun Oxcat-2 and most of those for Sun Oxcat-1. Sun Oxcats 3 and 4 are in still the research stage.

5.1 Summary of Process Development Activities

Studies were conducted in both one-step oxidation of isobutane, and in optimization of the second step of the two step oxidation process (Figure 5-1). The main product of oxidation is t-butyl alcohol (TBA). The second step is the decomposition of t-butyl hydroperoxide (TBHP). The catalysts we are testing are various Fe(III)-macrocyclic complexes.

We reported previously that catalyst cost for hydroperoxide decomposition under a set of desired operating conditions was in the range of 2-5 c/gal MTBE for our proprietary catalyst SUN-Z'. In a stainless steel reactor @ 80-120°C, 0-200 psig, and 30 mole % TBHP in t-butyl alcohol(TBA), the conversion of TBHP ranged from 60 to 98 mole % in 1 to 3 hrs. at catalyst concentration of 15-200 ppm.

ISOBUTANE OXIDATION-PROOF-OF-CONCEPT STAGE
PROCESS TECHNOLOGY DEVELOPMENTS
USING NEW SUN CATALYSTS

SUN OXCATS FOR PRODUCT/PROCESS FLEXIBILITY

SCHEME 1

FIGURE 5-1

Isobutane Oxidation for Reformulated Gasoline

We have continued to focus on further hydroperoxide decomposition studies with yet cheaper catalysts. The catalyst cost for the TBHP decomposition reaction with CAT-X and CAT-X' catalysts is calculated to be 0.5-1.5 c/gal MTBE. The operating performance and their lower cost make these catalysts suitable for use in a two-step commercial retrofit process for TBA production.

As we embarked on the first developmental Phase of the proof-of-concept stage of the Catalytic Conversion of Light Alkanes, we had catalysts which were nearing the kind of activity required of a commercial process for producing tert-Butyl alcohol, TBA, from isobutane. These catalysts are comprised of an iron center in an electron-deficient porphyrin macrocycle and are dissolved in the alkane substrate, isobutane, which when exposed to oxygen, is converted to TBA in good yield. For such a catalyst to be commercial, increases in activity and reduction of catalyst cost still had to be achieved. We recognized that when these goals were reached, not only would we have a catalyst practical enough to oxidize isobutane to TBA in an industrial process, but also one which is capable of oxidizing propane to isopropyl alcohol, IPA, at a rate sufficient to begin the proof-of-concept stage for propane oxidation. As each successive catalyst improvement creates a practical opportunity for a given hydrocarbon conversion, it will also provide the activity to begin to convert the next most difficult substrate, until at the end of the program that was originally envisioned, all components of natural gas including methane might be converted to the corresponding alcohol in a practical manner.

Conceptual economic analysis shows that an isobutane-to-TBA process operating on 12,000 B/SD of isobutane converting 50% of the feed to TBA in 92% selectivity could sustain an IRR of over 15%. A block diagram of this simple, one-step alkane to alcohol process using a soluble metalloporphyrin catalyst is shown in Figure 5-2.

The following sections demonstrate synthetic procedures for generating second generation catalysts based on nitroporphyrins, initial testing of these catalysts and Process Development work on first generation catalysts which we can make in large quantities. We have completed the goal of synthesis of 10g of the first generation catalyst which will be reported in the second 1993 Quarterly Report.

5.1.1 TBA Process Research - A One-Step Oxidation of Isobutane to TBA M. V. Bhinde and S. Baker

5.1.1.1 Isobutane Oxidation Using a Perhaloporphyrin Catalyst

The catalyst: $\text{Fe}(\text{TPPF}_{20}\text{Cl}_3) \text{ X}$ ($\text{X} = \text{Cl}, \text{OH}$) was used for initial reactor shake down, developing standard procedures and training of new employees. A GC was incorporated in the high pressure bay to obtain on-line product analyses. Reactions were carried out @ 80°C, 200-400 ppm catalyst concentration and 30-150 psia O_2 partial pressure. Isobutane conversion was limited to ~35%, TBA being the major product (~80%) of oxidation. Pseudo-first order rate constants for isobutane conversion were found to be 200-400 l/(g mole cat-h). O_2 partial pressure has less of an impact on the rate of reaction than previously thought.

Figure 5-2

Isobutane Oxidation
Schematic of One-Step Process

Addition of a small amount of a proprietary additive to the reaction medium prolongs the duration of oxygen uptake with minor impact on the rate of O₂ uptake. Isobutane conversion as high as 63% has been achieved for the first time with these catalysts, resulting in turnover number of >30,000.

5.1.1.1.1 Introduction

In the alkane to alcohol project, isobutane oxidation is being studied in a high pressure batch autoclave using porphyrin based catalysts. The study is aimed at developing design basis data for grass routes and retrofit commercial scale oxidation processes. The work includes establishing performance targets defining and optimizing reactor/catalyst performance, and establishing feed and product specifications.

5.1.1.1.2 Data & Experimental Procedures

The reactor is a 500 cc autoclave located in a barricaded chamber. Typically, the catalyst, along with any co-solvent, is charged into the reactor before sealing. Isobutane is charged using a 300 cc Hoke bomb. The O₂ addition and temperature control are accomplished from outside the barricade. Instrument/Research grade isobutane is being used for all of the studies. The typical purity is 99.7 % isobutane with propane and n-butane being the major impurities. The isobutane/catalyst/co-solvent is heated to the desired reaction temperature in the presence of nitrogen. Oxygen is then added at the desired partial pressure to initiate the reaction. (Nitrogen pressure is such that O₂ partial pressure will be <10 % of total pressure to avoid vapor phase explosive conditions). The oxygen partial pressure is then maintained within a 5-10 psi range by means of total pressure controller. A recirculating loop involving a pump and a GC sample valve are incorporated in the system to accomplish on-line analyses to follow the reaction.

5.1.1.1.3 Results & Discussion

We have a joint program underway with a major chemical company to develop catalyst/process for isobutane oxidation. Technical targets for the catalyst performance have been established for isobutane oxidation for a retrofit opportunity in an existing oxidizer. for this discussion, the important target is the requirement that pseudo first order rate constant be 0.07/h @ 30% isobutane conversion in a cstr reactor.

5.1.1.1.4 Initial Runs

Run #104141, 51, and 61 were carried out @ 80°C, 45 psia average O₂ partial pressure, 520 psig total pressure, and ~295 ppm catalyst concentration. Figures 1 - 4 show typical product distribution (#104141) as a function of reaction time. As can be seen, isobutane conversion reached about 35 mole % after 6 hrs. t-Butyl alcohol is the major product (~80 mole %) along with acetone (~14 mole %). The reaction does not follow a true first order kinetics, but for engineering purposes the the data are presented for initial and final period as first order plots in Figures 5 and 6. The initial and final pseudo first order rate constants were found to be 0.078 and 0.036 /h, respectively. At 295 ppm catalyst concentration these translate into 212 and 98 l/g mole cat/h, respectively.

FIGURE 1

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst (*Fe*. Catalyst) IC4=2391mm

FIGURE 2

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst: (*Fe* Catalyst) IC4=2391mm

FIGURE 3

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst: (Fe Catalyst) IC4=2391mm

FIGURE 4

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst: (Fe Catalyst) IC4=2391mm

FIGURE 5

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst (Fe Catalyst) IC4=2391mm

$$\ln(C/C_0) = -0.078 * t \text{ (h)}$$

FIGURE 6

OXIDATION OF ISOBUTANE

Run 1004141 Catalyst: (Fe Catalyst) IC4=2391mm

Run #104157, 64, and 66 were carried out @ 135, 90 and 25 psia, respectively. The concentration of TBA as a function of reaction time is presented in Figure 7 and the data indicate a slight negative effect of O₂ pressure. This is contrary to previous understanding, which was based on rates of O₂ uptake during a very short (15 min) initial reaction period. Further studies will be carried out to establish O₂ pressure effects.

5.1.1.1.5 Addition of a Proprietary Additive

A small amount of a proprietary additive was added in run #104169. It was hypothesized that small amounts of organic acids and water being produced may affect catalyst activity at 30 + % i-C₄ conversion. Also, if the catalyst is a mixture of two forms containing chloride and proprietary axial ligands, the proprietary additive will help convert the chloride into the proprietary form. The concentration of TBA as a function of reaction time is presented in Figure 8. Note that although the initial rate of formation of TBA was about the same as that without the proprietary additive, the ultimate conversion of isobutane was ~53 % after about 16 hrs. This represented over 30,000 turnovers (moles i-C₄ reacted/mole catalyst).

Several exploratory experiments have been carried out with the proprietary additive to further understand this effect; however, it is still not clear how it helps achieve higher conversion of isobutane. Among other postulates to explain the observation are alteration of hydrophilic/lipophilic properties, ionic strength, stacking of catalyst molecules, and facilitating break up of μ -oxo dimer. Run #1004178, also presented in Figure 8, was carried out with 750 ppm catalyst instead of 300 ppm, and it achieved i-C₄ conversion of ~63 % after ~16 hrs.

5.1.1.1.6 Effects of Catalyst Concentration

Effect of catalyst concentration in the charge is summarized in Table I. Reactions 1004187, 1004209, 1004210 and 1004265 were carried out @ 80°C, 45 psia average O₂ partial pressure and ~600 psig total pressure. The catalyst concentration was varied from 0 to 13 ppm (mole/mole). The isobutane conversion increased with catalyst concentration, but increase was less than proportional.

5.1.1.1.7 Effect of Water

Run # 1004187, 4239, and 4257 were carried out @ 80°C and 45 psia O₂ pressure with varying amounts of water in the reactor charge. The conversion to TBA decreases with increased amount of water (Table II), but the effect is small for typical levels of water found in isobutane.

5.1.1.1.8 Effect of NaOH

Addition of a small amount of conc. NaOH helps achieve higher conversion of isobutane. Several runs were carried out with varying amounts and concentration of NaOH in the reactor charge.

FIGURE 7
OXIDATION OF ISOBUTANE
EFFECT OF O₂ PARTIAL PRESSURE

16

FIGURE 8
OXIDATION OF ISOBUTANE

TABLE I
ISOBUTANE OXIDATION
Fe[PPF20Cl8]OH CATALYST, 80 C, 45 PSIA O2
EFFECT OF CATALYST CONCENTRATION

REACTION #	ISOBUTANE g	CATALYST mg	CATALYST CONC m cat/m iC4	CONVERSION %	TBA %	TIME min
1004209*	131.9	0	0.00E+00	5.3	3.7	250
1004214	138.9	0	0.00E+00	4.0	3.6	303
1004265	131.5	20	6.60E-06	32	27	460
1004187	134.9	40	1.29E-05	36	30	370

* Contains 0.8 g H2O; produced more acetone by-product.

TABLE II

ISOBUTANE OXIDATION
Fe[PPF20Cl8]OH CATALYST (28 mg/100 g), 80 C, 45 PSIA O₂,

EFFECT OF WATER

REACTION #	CATALYST CONC m cat/m iC ₄	WATER CONC g/100 g	CONVERSION %	TBA %	TIME min
1004187	1.29E-05	0.0000	36	30	370
1004257	1.32E-05	0.0015	33	26	360
1004239	1.24E-05	0.0063	32	26	380

The results in Table III show that the reaction rate of isobutane oxidation decreases with increasing amount of 8 N NaOH, but the final conversion of isobutane reaches a maximum around 2 vol %.

The results in Table IV show that conversion of isobutane increases with the strength of NaOH at least up to 8 N conc.; however, with dry NaOH the reaction comes to stop within 1 hour with less than 5% conversion. The reaction rate is 20-50% lower in the presence of NaOH.

As a variation to study NaOH effect, a batch of catalyst dissolved in toluene was pretreated with aqueous NaOH at room temperature for two hours and then dried by rotavap. This catalyst had higher activity for isobutane oxidation when fresh but lost it upon aging over several days (Table V).

Several other exploratory experiments have been carried out with NaOH to further understand this effect; however, it is still not clear how NaOH helps achieve higher conversion of isobutane. Among other postulates to explain the observation are alteration of hydrophilic/lipophilic properties, ionic strength, stacking of catalyst molecules, and facilitating break up of μ -oxo dimer.

5.1.1.1.9 Effect of Added Olefins

Reactions were carried out in the presence of 1-butene and isobutylene using NaOH treated catalyst. There was not much effect on rate or conversion @ 100 ppm olefin concentration (Table VI).

5.1.1.1.10 Effect of Added Acid

Addition of 1.5% isobutyric acid resulted in increased conversion of isobutane to 40% w/ 32% yield of TBA (Table VI).

5.1.1.1.11 Effect of Solvents

Reactions were carried out in the presence of Freon 113 (60 wt %), acetonitrile (10 and 50 vol %), and Acetone (40 wt %) to see if higher catalyst solubility will benefit the reaction rate. In all cases there was no beneficial effect of the solvent on reaction rate or ultimate isobutane conversion. Usually the final conversion was lower (Table VI).

5.1.1.1.12 Effect of Catalyst Aging

Since we have shown that catalyst slurring (in acetone) and aging help the oxidation activity with SUN-Z', several experiments were carried out to see if the activity enhancement is possible with our best catalyst $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$ for isobutane oxidation.

TABLE III
 ISOBUTANE OXIDATION
 Fe[PPF20Cl8]OH CATALYST (28 mg/100 g), 80 C, 45 PSIA O₂,
 EFFECT OF 8 N NaOH

REACTION #	CATALYST CONC m cat/m iC ₄	NaOH AMOUNT g/100 g	CONVERSION %	TBA %	TIME min
1004187	1.29E-05	0.00	36	30	370
1004272	1.43E-05	0.66	40	32	580
1004169	1.40E-05	4.97	54	44	954
1004274	1.35E-05	9.90	44	36	780
1004277*	1.35E-05	0.64	30	25	360

* Contains 20 mg of 18-6, Crown ether.

TABLE IV

ISOBUTANE OXIDATION
 Fe[PPF20Cl8]OH CATALYST (28 mg/100 g), 80 C, 45 PSIA O₂,
 EFFECT OF NaOH STRENGTH (~0.6 g/100 g isobutane)

REACTION #	CATALYST CONC m cat/m iC ₄	NaOH STRENGTH Normality	CONVERSION %	TBA %	TIME min
1004239	1.24E-05	0.0	32	26	380
1004264	1.27E-05	1.6	30.6	25.3	360
1004272	1.43E-05	8.0	40	32	580
1004200*	1.20E-05	Pellets	5.5	4.7	207

* 4 g dry NaOH pellets added; water is produced as the reaction proceeds.

TABLE V

ISOBUTANE OXIDATION

Fe[PPF20Cl8]OH CATALYST (28 mg/100 g), 80 C, 45 PSIA O₂,

EFFECT OF NaOH PRETREATMENT OF CATALYST

REACTION #	CATALYST CONC m cat/m iC ₄	NaOH PRETREAT	CONVERSION %	TBA %	TIME min
1004187	1.29E-05	N	36	30	370
1004210*	1.25E-05	Y, fresh	38	31	350
1004225	1.34E-05	Y, aged	36	29	580
1004269	1.34E-05	Y, aged	36	30	720

* Reaction was continued beyond 350 min @ 50-100 psi O₂ pressure: Final conversion was 42.6 % w/ 34.6 % TBA

TABLE VI
 ISOBUTANE OXIDATION
 Fe[PPF20Cl8]OH CATALYST (28 mg/100 g), 80 C, 45 PSIA O2,
 MISC RUNS W/ NaOH PRETREATED AND UNTREATED CATALYST

	REACTION #	CATALYST CONC m cat/m iC4	OTHER COMPONENT	CONVERSION %	TBA %	TIME min
NaOH pretreated catalyst	1004225	1.34E-05	None	36	29	580
	1004228	1.20E-05	100 ppm 1-C4=	35	29	635
	1004262	1.16E-05	100 ppm i-C4=	32	26	680
	1004218*	1.61E-05	58 w% Freon113	24	20	440
	1004220*	1.58E-05	40 wt% Acetone	18	13	260
Untreated catalyst	1004260*	1.51E-05	1.7wt % i-buacid	40	32	440
	1004268*	1.38E-05	5.7 wt % ACN	28	21	280
	1004267*	2.40E-05	51 wt % ACN	26	17	360

* Cat conc /unit vol is approximately constant in all runs @ 1.5E-07 moles/cc

Several experiments were carried out with $\text{Fe}[\text{PPF}_{20}\text{C}_{18}]\text{OH}$ slurried and aged in acetone as shown in Table VII. It was found that the initial pseudo first order rate constant was virtually the same (~ 0.12 /h) in all cases. Acetone does tend to inhibit the isobutane oxidation reaction at higher conversion; final conversion to TBA in all experiments in the presence of acetone was less than that achieved in the absence of acetone. We see no advantage of acetone with this catalyst.

The activity of $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$ is not sufficient to help us achieve our goals for a grass root isobutane oxidation facility (Table VIII), but is sufficient to be used as a catalyst in a retrofit operation of current commercial oxidation reactors. The cost of this catalyst, however, is prohibitive.

5.1.1.1.13 Sodium Dithionite Effect

We have reported that oxidation of isobutane with $\text{Fe}[\text{PPF}_{20}\text{C}_{18}]\text{OH}$ catalyst results in ~ 35 % isobutane conversion with 29 mole % TBA in 6 hours. It was found that after many runs performance had dropped to ~ 30 % conversion and ~ 24 % TBA yield. It is not clear if this was due to activity of reactor walls, aging of the catalyst, or trace contamination of the feed. Addition of 10-20 mg of sodiumdithionite seems to help achieve baseline results (Table IX). Larger addition of Na dithionite results in poorer performance. Na dithionite is a strong reducing agent. We further explore whether the reducing agent is affecting the catalyst or the reactor walls.

5.1.1.2 Isobutane Oxidation Using $\text{Fe}[\text{PPF}_{16}]$ as Catalyst

Several batches of the new catalyst $\text{Fe}[\text{PPF}_{16}]$ were tested for isobutane oxidation activity. Isobutane conversion and TBA yield were higher for the μ -oxodimer form of the catalyst as compared to $\text{Fe}[\text{PPF}_{20}\text{C}_{18}]\text{OH}$ catalyst. The monomer as chloride is less active than either (Table X). The rate of reaction was $\sim 1/3$ that of $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$ catalyst.

5.1.1.3 Isobutane Oxidation Using $\text{Fe}[\text{PP}(\text{C}_2\text{H}_5)_8](\text{NO}_2)_4$ as Catalyst

Fe tetranitrooctaethylporphyrin was tested in the dimer form for isobutane oxidation activity. This catalyst was found to have performance similar to that of $\text{Fe}[\text{PPF}_{16}]\text{Cl}$ for conversion, yield and rate (Table X).

5.1.1.4 Isobutane Oxidation Using Catalyst SUN-Z'

Isobutane oxidation was carried out using SUN-Z' catalyst at 80°C and 10-50 psi O_2 partial pressure. Formation of TBA and disappearance of isobutane are followed with time by means of on-line GC. Typical concentration profiles are shown in Figures 6 and 7 (Run # 1010762). The catalyst for this run was slurried in acetone and the slurry aged for over 3 days before reaction. Note that no induction period was observed, and the initial pseudo first order rate constant for the disappearance of isobutane was found to be 0.013 /h. This is about an order of magnitude less than that reported for $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$ catalyst (3rd quarter 1993 report).

TABLE VII

ONE-STEP OXIDATION OF ISOBUTANE USING CATALYST $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$
 80 C, 35 psia O_2 , 260 ppm catalyst

RUN #	ACETONE	CATALYST	K-ACETATE	WATER	INITIAL	NOTES
	wt %	slurried & aged?	ppm	ppm	1st order k 1/h	
1004187	0	N	N	N	0.14	IC4 conv $\approx$ 30 % in 4 hrs, but max ~ 36 % in 6 hrs
1010772	10	N	1800	1800	0.12	Max IC4 conv $\approx$ 17 % in 2 hrs.
1010779	10	Y	N	N	0.11	Max IC4 conv $\approx$ 22 % in 4 hrs.
1010780	3.7	Y	1800	1800	0.12	Max IC4 conv $\approx$ 26 % in 4 hrs.
1010776	10	Y	N	8 N NaOH (4 %)	0.13	IC4 conv $\approx$ 23 % in 4 hrs, but reaction continues

TABLE VIII

PERFORMANCE TARGETS FOR ONE-STEP OXIDATION OF ISOBUTANE
80 C, 30-50 psia O₂, 500-600 psig total pressure

	GRASS ROOTS	RETROFIT	CURRENT BEST
IC4 Conv, %	50 +	30 +	30 +
Reaction Time, h	2.5	5	5
TBA Selectivity, %	90 +	85 +	80 +
Cat cost, c/gal MTBE	<3	< 5	>50

TABLE IX
 ISOBUTANE OXICATION
 EFFECT OF Na dithionite

80°C, 45 psia O₂, 285 ppm Fe[PPF₂₀Cl₈]OH

REACTION#	Na ₂ H ₂ S ₄ mg	IC ₄ CONV. mole %	TBA YIELD mole %	TIME min
1,000,719	0	29.6	24.4	360
1,000,715	10	36.4	29.0	745
1,000,701	19	38.5	31.4	500
1,000,711	42	20.5	17.2	280
1,000,709	100	23.0	19.4	630

TABLE X
ISOBUTANE OXIDATION
SCREENING OF NEW CATALYSTS

80° C, 45 psia O₂, 285 ppm catalyst

REACTION #	CATALYST ID	IC ₄ CONV. mole %	TBA YIELD mole %	TIME min
1004187	F20C18	36	30	370
1004232	F16DIMER	41	33	1260
1004292	F16 dimer	43	36	1140
1000717	F16 monomer(CI)	28	24	980
1000726	F16 dimer	43	36	1300
1000705	TNOEP	31	25	1100

FIGURE 6

OXIDATION OF ISOBUTANE, RUN 1010762

80 C, 45 PSIA O₂, SUN-Z' :40 mg slurried in 15 g dry acetone

FIGURE 7

OXIDATION OF ISOBUTANE, RUN 1010762

80 C, 45 PSIA O₂, SUN-Z' : 40 mg slurried in 15 g dry acetone

Based on our experience with SUN-Z' in TBHP decomposition (1st, 2nd Quarterly reports, 1994), several variations of operating conditions were studied including lower O₂ partial pressure, acetone/ co-solvent concentration, and addition of TBHP (~1 %) to kick off the oxidation reaction. The results are summarized in Table XI.

What we found was:

1. The initial first order rate constant was increased to 0.03 /h when the catalyst was slurried in freon 113 solvent, and acetone and isobutyric acid were added as co-solvents. (Run # 1010755, Figures 8 and 9).
2. When powder SUN-Z' catalyst is added along with acetone co-solvent (without prior slurrying and aging), a ~2 hr induction period is observed, and first order rate constant was always less than 0.01 /h. (Run# 1010761, Figures 10 and 11).
3. With the aged catalyst slurry of SUN-Z', the first order rate constant is increased to 0.029 by injecting ~1 g of TBHP to the reaction mixture after the reaction is underway. (Run # 1010753, Figures 12 and 13).
4. When powder SUN-Z' catalyst was added without acetone co-solvent but in the presence of Potassium acetate buffer, no induction period was observed, and the initial pseudo first order rate constant was 0.014 /h @ 30 psia O₂ partial pressure. (Run # 1010760, Figures 14 and 15).
5. When powder SUN-Z' catalyst was added with larger amount of acetone co-solvent (40 g instead of 15 g) and in the presence of Potassium acetate buffer, no induction period was observed, and the initial pseudo first order rate constant was 0.024 /h. (Run # 1010759, Figures 16 and 17).

TABLE XI

ONE-STEP OXIDATION OF ISOBUTANE USING CATALYST SUN-Z'
80 C, 40 psia O₂, 260 ppm catalyst

RUN #	ACETONE CATALYST-K-ACETATE			WATER		INITIAL 1st order k 1/h	NOTES
	wt %	aged?	ppm	ppm	ppm		
1010762	10	Y	N	N	N	0.013	No boost due to TBHP addition at 4-5 hrs.
1010765	10	Y	N	N	N	0.03	Catalyst slurried in freon 113; ~7 % acetone, 1.5 % isobutyric acid
1010761	0	N	N	N	N	<0.01	~2 hr induction period
1010753	10	Y	N	N	N	0.029	After adding 0.7 % TBHP; 21+ % conv of IC4 @ 12 hrs = 11200 T.O.
1010760	0	N	1800	7400	7400	0.014	@ 30 psia O ₂
1010759	23	N	1400	5700	5700	0.024	@ 30 psia O ₂ ; ~6 % max conv of IC4 at 5 hrs.

OXIDATION OF ISOBUTANE, RUN 1010755

80 C (120 C after 800 min), 45 PSIA O₂, SUN-Z'

Catalyst slurried in freon113 (8 g), 10 g acetone, 2 g isobutyric acid
Restart @ 340, 760 and 1130 min

Figure 8

OXIDATION OF ISOBUTANE, RUN 1010755

80 -120C, 45 PSIA O2, SUN-Z'

Figure 9

OXIDATION OF ISOBUTANE, RUN 1010761

80 C, 45 PSIA O₂, SUN-Z'

Figure 10

■ TBA ♦ Data B

OXIDATION OF ISOBUTANE, RUN 1010761

80 C, 45 PSIA O₂, SUN-Z'

Figure 11

Figure 12

OXIDATION OF ISOBUTANE, RUN 1010753

80 C, 45 PSIA O₂, 40 mg SUN-Z' in 15 g acetone

OXIDATION OF ISOBUTANE, RUN 1010753

80 C, 45 PSIA O2, SUN-Z'

Figure 13

OXIDATION OF ISOBUTANE, RUN 1010760

80 C, 30 PSIA O₂, 40 mg SUN-Z' in 15 g acetone; 250 mg Kacetate, 1 g water

Figure 14

Figure 15

OXIDATION OF ISOBUTANE, RUN 1010760

80 C, 45 PSIA O₂, SUN-Z'

Figure 16

OXIDATION OF ISOBUTANE, RUN 1010759

80 C, 30 PSIA O₂, 40 mg SUN-Z' + 40 g acetone+250 mg KAcetate +1 g water

Figure 17

OXIDATION OF ISOBUTANE, RUN 1010759

80 C, 30 PSIA O₂, SUN-Z'

Based on the above results we conclude that SUN-Z' is an active catalyst for isobutane oxidation, and its activity can be enhanced by slurring in acetone co-solvent, aging the slurry, addition of potassium acetate buffer and/or addition of TBHP initiator. We have shown turnover numbers as high as 11,200 moles isobutane reacted /mole of catalyst over a 12 hr reaction time (Run # 1017053). However, the initial pseudo first order rate constant was never greater than 0.03 /h, which is about one quarter of that observed with our best catalyst Fe[PPF₂₀Cl₈]OH catalyst.

5.1.1.5 Catalysts CAT- X and CAT-X'

These two catalysts were identified as inexpensive and active catalysts for TBHP decomposition (see section below) during the last quarter. We also evaluated them for the direct one-step oxidation process in several experiments. The results are summarized in Table XII.

At 80°C and 30-50 psia O₂ partial pressure, we found isobutane oxidation activity for CAT-X and CAT-X' to be about 20 % lower than that of SUN-Z' at the same catalyst concentration (w/w). Doubling their concentration did not improve the first order rate constant by more than 20 %. Thus although these catalysts are significantly cheaper than SUN-Z' and other catalysts we have tested, they are not suitable for the direct oxidation reaction.

5.1.2 TBA Process Research-A Two-Step Oxidation of Isobutane to TBA

M. V. Bhinde, J. E. Lyons, S. Baker and R. Carter

Efforts were directed to study the second step of the two-step process for isobutane oxidation. The second step is the decomposition of t-butyl hydroperoxide (TBHP). It is known that isobutane can be oxidized non-catalytically to tert-butyl hydroperoxide, TBHP, eq. 1. If one could rapidly and selectively decompose TBHP to tert-butyl alcohol, TBA, eq. 2., a potentially practical process from isobutane to TBA could be developed. The catalysts we are testing for the second step are proprietary Fe(III)-macrocyclic catalysts. The main product of oxidation is t-butylalcohol (TBA).

This study is aimed at developing design basis data for grass roots and retrofit commercial scale oxidation processes. The work includes establishing performance targets, defining and optimizing reactor/catalyst performance, and establishing feed and product specifications. Schematic flow diagram the two-step processes are shown in Figure 18.

TABLE XII

ONE-STEP OXIDATION OF ISOBUTANE USING CAT-X & CAT-X'
80 C, 30-50 psia O₂

RUN #	ACETONE wt %	CATALYSTK-ACETATE slurried & aged?, ppm	ppm	WATER ppm	INITIAL 1st order k 1/h	NOTES
1010770	10	Y, 260	N	N	0.022	CAT-X; 40 psia O ₂
1010769	10	Y, 530	1800	1800	0.024	CAT-X; 40 psia O ₂
1010767	5	Y, 530	1800	1800	0.018	CAT-X'; 20-40 psia O ₂
1010764	10	Y, 530	N	N	0.024	CAT-X'; 40 psia O ₂
1010773	10	Y, 530	N	8N NaOH (4 %)	0.03	CAT-X'; 40 psia O ₂ 40 min induction period

Figure 18

Isobutane Oxidation
Schematic of Two-Step Process

ABSTRACT

We have made excellent progress toward a practical route from field butanes to MTBE, the oxygenate of choice for high-octane, clean-burning, environmentally acceptable reformulated gasoline. We have evaluated two proprietary process possibilities with a potential commercial partner and have conducted a joint catalyst evaluation program.

The first of the two potential processes considered during the past quarter utilizes a two-step route from isobutane to tert-butyl alcohol, TBA. Not only is TBA an intermediate for MTBE production but is equally applicable for ETBE- an oxygenate which utilizes renewable ethanol in its manufacture. In the two-step process, isobutane is oxidized in a non-catalytic reaction to a roughly equal mixture of TBA and tert-butyl hydroperoxide, TBHP, eq. 1. We have developed an inexpensive new catalyst system based on an electron-deficient macrocyclic metal complex that selectively converts TBHP to TBA, eq. 2, and meets or exceeds all of the process criteria that we have set.

The second process concept directly reacts isobutane with oxygen to give TBA in a single step, eq. 3. We continue to make progress on this reaction. Sun patented catalysts are the most active of any known for this reaction. A major hurdle which must still be overcome is that of catalyst cost. Catalysts effective for the one step reaction are still too costly for industrial production. New catalysts have been synthesized for the first time which hold the promise to solve this problem if they are active enough.

Figure 18

Isobutane Oxidation Schematic of Two-Step Process
(Page 2)

Technical and economic targets have been set for the catalyst performance for TBHP decomposition in a two step process. The relevant targets for the current discussion are as follows:

1. TBHP conversion to be 98 % minimum.
2. Reaction time of 1 hr in a batch reactor.
3. Selectivity for TBA to be >85 %.

5.1.2.1 Experimental Procedures Composition for t-Butylhydroperoxide

The reactor is a 50 cc autoclave located in a barricaded chamber. TBHP and TBA are charged to the reactor, which is sealed and pressure tested. A nitrogen purge system is used to avoid build up of O₂ in the reactor and not create an explosive vapor phase mixture. The gas flow in and out are metered to follow the decomposition reaction. The final product is analyzed by gas chromatography. The temperature control and flow readings are accomplished from outside the barricade. The catalyst is held as a solution in TBA. When the reactor temperature is stable, a valve is opened to allow the catalyst solution to be injected into reactor.

5.1.2.2 Results & Discussion

A number of reactions are summarized in Table XIII. Typically, the decomposition reaction is very rapid with all of the catalysts tested. At 80°C and less than 30 ppm catalyst, >80 % TBHP is decomposed in less than 2 hours. The major product of decomposition is TBA, with acetone and di-*t*-butylperoxide being the minor products. For all of the catalysts, the conversion is slightly lower at 100 and 120 C, even though the blank reactor activity increases at this higher temperatures, suggesting that the catalysts themselves are not stable at elevated temperature.

A typical experiment (#1012455) involved a reaction of 37.7 wt % TBHP in TBA @ 80°C, 200 psig total pressure and 10 cc/min N₂ sweep flow. Once the reaction conditions were stabilized, a 0.8 g of catalyst (Sun-2: Fe[PPF₂₀Cl₈]OH) solution in TBA was injected in the reactor. The gas flow in and out were followed as shown in Figure 19. Typically, the reaction starts instantaneously; however, there is an apparent induction period seen in Figure 19. This is due to O₂ being used up in saturating the reacting liquid.

The final product from experiment # 1012455 was analyzed by gas chromatography. 97.2 % of TBHP was converted in 2 hrs. The major reaction product was TBA, with acetone and di-*t*-butylperoxide being by-products. The selectivity for TBA was ~87 %.

The concentration of TBHP was back calculated from the volume of gas produced, and is plotted in Figure 20. Again, there is an apparent induction period in the first 10 minutes. The GC and calculation procedures are being improved to get a better handle on reaction kinetics.

TABLE XIII
TBHP DECOMPOSITION

RUN #	CAT.	CAT conc ppm	TEMP C	%TBHP in product	CONV mole%	TIME min	PRES. psig
2407	SUN-X	29	80	4.9	84	60	600
2410	SUN-X	58	80	0.8	97	35	600
2412	SUN-X	29	120	2.3	93	20	600
2414	SUN-X	58	80	1.0	97	30	200
				0.4	99	4 weeks later	
2416	BLANK0		120	13.6	56	30	600
2419	BLANK0		80	27.4	11	30	600
2421	SUN-2	58	60	13.1	57	180	600
				0.3	99	3 days later	
2424	SUN-Y'	29	80	1.9	94	120	600
				0.5	98	2 weeks later	
2427	SUN-Y'	29	120	5.2	83	60	200
				5.5	82	2 weeks later	
2430	SUN-Y	29	80	2.6	92	120	600
2432	SUN-Y	29	120	4.1	87	90	200
2438	SUN-X	29	80	2.5	92	70	200
				2.4	92	11 days later	
2445	BLANK0		120	11.7	62	30	200
2447	SUN-X	27	80	2.6	93	60	200
2449	SUN-Y'	29	100	4.0	87	80	200
				2.7	91	After 4 weeks	

SUN-X = FeTNOEP

SUN-Y = Fe[PPF16] dimer

SUN-Y' = Fe[PPF16]Cl monomer

SUN-2 = Fe[PPF20Cl8]OH

FIGURE 19

TBHP DECOMPOSITION

80 C, 29 ppm SUN - 2, 1012455

FIGURE 20

TBHP DECOMPOSITION, 1012455

80 C, 29 ppm SUN-2

In a similar experiment with the Sun-Z' catalyst, a new proprietary catalyst composition, (experiment # 1013909) at atmospheric pressure, the O₂ production is instantaneous (Figures 21 & 22).

A number of reactions were carried out at 80 and 120°C using various catalysts, which are summarized in Table XIV. The stainless steel has significant activity @ 120°C, thus requiring use of a glass liner (Blank runs 2478 and 2471). For all catalysts, the final conversion achieved is lower @ 120°C than that at 80°C, suggesting that these catalysts break down @ 120°C at a much faster rate.

The catalyst Sun-Z' is very insoluble in TBA; hence in experiment # 3905, 3907, 3909 and 3911 in Table XIV, the reactions were carried out with catalyst in the reactor and the reagent TBHP was injected into the reactor when reaction conditions were stabilized. Reactions were tried in the presence of acetone cosolvent to enhance solubility of the catalyst. As can be seen from Table XIV, the reaction rate increased 3-4 fold with Sun-Z' in the presence of 9 wt % acetone (3911 vs 3905). Also the O₂ pressure has inhibitory effect on the catalyst performance as seen from experiments 3909 and 3911.

5.1.2.2.1 Reaction Kinetics

Several experiments were carried out in a glass reactor at atmospheric pressure to follow the kinetics of hydroperoxide decomposition reaction. In each case, the reaction was carried out @ 75-80°C, with a reflux condenser. The catalyst (as powder or slurried in TBA or acetone) was added when the reaction conditions are stabilized, and the O₂ uptake was followed.

A typical O₂ production curve is shown in Figure 23. From the O₂ measurements, the moles of TBHP reacted are calculated in Table XV. The calculated concentration of TBHP is plotted against reaction time in Figure 24. A semi-log plot of conc vs time is shown in Figure 25. Note that the reaction does not follow a first order kinetics. This is due to the fact that the catalyst itself is decomposing. One measure of relative catalyst activity is its initial pseudo-first order rate constant calculated from the initial slope in Figure 25. In this case, the initial first order rate constant is 0.24 /min, or 3996 l/mole cat/min.

Initial rate constants for several catalysts are shown in Table XVI. Sun-X is the most active catalyst initially, but it decomposes rapidly. Sun-2 and Sun-Y have about the same activity initially, but Sun-2 is stable whereas Sun-Y decomposes rapidly. Sun-Z' does not exhibit much activity by itself (Run # 1005273), but is comparable to others in the presence of acetone. Sun-Z' is believed to be the least expensive of all of the catalysts, and further work is planned to characterize its performance.

SUN-X = FeTNOEP

SUN-Y = Fe[PPF₁₆] dimer

SUN-Y' = Fe[PPF₁₆]Cl monomer

SUN-2 = Fe[PPF₂₀Cl₈]OH

SUN-Z' = proprietary

TBHP DECOMPOSITION, 1013909
80 C, 59 ppm SUN-Z'

FIGURE 21

TBHP DECOMPOSITION

80 C, 59 ppm SUN - Z', 1013909

FIGURE 22

TABLE XIV

TBHP DECOMPOSITION

SUMMARY OF RUNS: 10/1/93 to 12/31/93

RUN #	CATALYST	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	CATALYST ppm acetone-free	Note
2478	BLANK	120	15.4	120	200	0	(GLASS LINER)
2471	BLANK	80	10.0	120	200	0	
2455	SUN-2	80	97.2	120	200	29	
2457	SUN-2	100	93.3	90	200	29	
2485	SUN-2	120	71.6	180	200	29	(GLASS LINER)
2487	SUN-2	120	89.7	180	200	29	(METAL Reactor)
2494	SUN-X	120	75.9	180	200	20	(GLASS LINER)
3900	SUN-X	80	83.5	180	200	14	
2492	SUN-X	80	85.2	180	200	19	
2452	SUN-X	80	78.3	90	200	19	
2497	SUN-X	80	93.1	180	200	29	
3902	SUN-X	80	97.6	180	200	29	
2459	SUN-Y'	80	95.4	120	200	29	
2449	SUN-Y'	100	87.2	80	200	29	
2480	SUN-Y	120	66.3	120	200	29	(GLASS LINER)
2474	SUN-Y	80	68.2	130	200	29	
2476	SUN-Y	120	82.6	120	200	29	(METAL Reactor)
2464	SUN-Y',Brx	120	85.1	90	200	29	(GLASS LINER)
2462	SUN-Y',Brx	80	85.6	90	200	29	
2469	SUN-Y,Brx	120	87.1	150	200	29	(GLASS LINER)
2467	SUN-Y,Brx	80	82.4	120	200	29	
3905	SUN-Z'	80	78.4	335	200	90	Cat in Rx
3907	SUN-Z'	120	61.0	135	200	90	Cat in Rx
3909	SUN-Z'	80	84.0	40	0	64	Cat in Rx; 9 % acet
3911	SUN-Z'	80	72.4	195	200	64	Cat in Rx; 9 % acet

FIGURE 23

TBHP DECOMPOSITION

RUN 1005269, 51 ppm SUN-Z', 77 C, 40 % TBHP/60 % TBA

TABLE XV

TBHP DECOMPOSITION
 RUN 1005269
 CATALYST - Fe[FPC]Cl
 TEMPERATURE 80 C
 DATE NOV 11, 1993
 CATALYST WT=

RUN # 1005269 JEL :11/15/93

	grams	mmoles	ml
ACETONE CHARGED=	3		3.9
TBHP CHARGED =	13.82	138.016	15.4
TBA CHARGED =	18.12	244.4684	22.9
1.8 mg	34.94		42.2

MAX O2 POTENTIAL @ 20 C =

1659.2

O2 YIELD =

1426.9 CON (O2)= 95.7%

O2 YIELD =

0.86 CON(GC)= 99.0%

TIME	ELAPSED TIME MIN	O2 EVOLVED CC	O2 EVOLVED mmoles	TBHP REACTED mmoles	TBHP REMAIN mmoles	TBHP CONC mmole/CC	Ln(C)	1/C	1/C-1/C0	PRED Ln(C) 0-5 min
14:09	0.00	0	0.00	0.00	138.02	3.27	1.19	0.3057	0.0000	1.18
14:10	1.00	280	11.65	27.08	110.93	2.63	0.97	0.3803	0.0746	0.94
14:11	2.00	560	23.29	54.17	83.85	1.99	0.69	0.5032	0.1975	0.70
14:12	3.00	760	31.61	73.51	64.51	1.53	0.42	0.6541	0.3484	0.45
14:13	4.00	900	37.43	87.05	50.96	1.21	0.19	0.8279	0.5222	0.21
14:14	5.00	990	41.18	95.76	42.26	1.00	0.00	0.9984	0.6927	-0.03
14:15	6.00	1060	44.09	102.53	35.49	0.84	-0.17	1.1889	0.8832	-0.28
14:16	7.00	1120	46.58	108.33	29.69	0.70	-0.35	1.4213	1.1156	-0.52
14:18	9.00	1190	49.49	115.10	22.91	0.54	-0.61	1.8413	1.5356	-1.01
14:20	11.00	1245	51.78	120.42	17.60	0.42	-0.87	2.3980	2.0922	-1.49
14:22	13.00	1280	53.24	123.81	14.21	0.34	-1.09	2.9692	2.6635	-1.98
14:25	16.00	1320	54.90	127.68	10.34	0.25	-1.41	4.0802	3.7745	-2.71
14:30	21.00	1345	55.94	130.09	7.92	0.19	-1.67	5.3255	5.0198	-3.92
14:42	33.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-6.84
15:00	51.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-11.22
15:15	66.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-14.87
15:35	86.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-19.73
16:00	111.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-25.82
16:30	141.00	1365	56.77	132.03	5.99	0.14	-1.95	7.0458	6.7401	-33.11

Regression Output: 0-5 min

Constant	1.183704
Std Err of Y Est	0.028749
R Squared	0.996817
No. of Observations	6
Degrees of Freedom	4

X Coefficient(s)	-0.24324 (1/min)
Std Err of Coef.	0.006872

FIGURE 24

TBHP DECOMPOSITION
RUN 1005269, 77 C, 51 ppm SUN Z', 40 % TBHP in TBA

FIGURE 25

TBHP DECOMPOSITION
RUN 1005269, 77 C, 51 ppm SUN Z', 40 % TBHP in TBA

TABLE XVI

TBHP DECOMPOSITION, 40 % TBHP IN TBA

RUN #	CATALYST	CAT conc, ppm	SOLVENT added	INITIAL k, 1/min
105178	SUN-2	19	None	0.030
105157	SUN-X	16	None	0.200
1005170	SUN-Y	19	None	0.024
1005253	SUN-Z'	16	Acetone, 9%	0.030
1005272	SUN-Z'	34	Acetone, 9%	0.110
1005276	SUN-Z'	51	Acetone, 9%	0.240
1005273	SUN-Z'	51	None	0.007

A typical experiment (#1013911) involved a reaction of 39.6 wt % TBHP in TBA with acetone co-solvent (9 wt % concentration) @ 80°C, 200 psig total pressure and 10 cc/min N₂ sweep flow. TBA and catalyst (SUN-Z') slurry along with co-solvent acetone were heated to 80°C @ 200 psig in the flow of nitrogen. Once the reaction conditions were stabilized, a 5.5 g of TBHP was injected in the reactor. The catalyst concentration was 59 ppm based on the total liquid in the reactor. The gas flow in and out were followed as shown in Figure 26. The difference between out and in flow is due to oxygen evolved from the decomposition reaction (Figure 27). Typically, the reaction starts instantaneously; in the Figure 26 and 27, there is an apparent induction period due to some of the oxygen being used up in saturating the reaction medium.

The final product from experiment # 1013911 was analyzed by gas chromatography. A 72.4 % of TBHP was converted in 195 minutes. The major reaction product was TBA, with acetone and di-t-butylperoxide being by-products. The selectivity for TBA was ~87 %.

The concentration of TBHP was back calculated from the volume of gas produced, and is plotted on a semi-log scale in Figure 28. Again, there is an apparent induction period in the first few minutes. The concentration-time curve is not a straight line on the semi-log plot for this catalyst. In the past we have obtained a linear plot for Fe[PPF₂OC₁₈]OH catalyst for this reaction suggesting that the catalyst itself is decomposing under this reaction condition. The GC and calculation procedures were improved to get better handle on reaction kinetics.

In a similar experiment with Sun-Z' catalyst (experiment # 1013909) at atmospheric pressure, the O₂ production appears to be instantaneous (Figures 29, 30 and 31) due to low pressure of the reaction.

A number of reactions were carried out @ 60-120°C using SUN-Z' catalyst, which are summarized in Table XVII. The stainless steel has significant activity @ 120°C, thus requiring use of a glass liner (Blank runs 2478 and 2471, 4th quarter, 1993 report). The final conversion achieved is lower @ 120°C than that at 80°C, suggesting that the catalyst breaks down @ 120°C at a much faster rate. The conversion @ 80°C is the maximum.

5.1.2.2.2 Effect of Co-Solvent on SUNZ'

Table XVIII shows the effect of added acetone on the decomposition of TBHP using SUN-Z' catalyst, at 80°C and pressure of 200 psig.

Table XVIII shows the benefit of the acetone addition on reaction rate and conversion. At 200 psig pressure, same level of TBHP conversion (78-80 %) can be achieved in about one half the time with one third less catalyst. Under these conditions, the conversion of TBHP, the catalyst consumption and the rate of reaction are all quite low compared to our target. Table XIX shows a similarly beneficial effect of ketonic co-solvents on reactions run in a glass reactor. In a number of instances first order rate constants were calculated. Reaction conditions are given in the footnotes.

FIGURE 26

TBHP DECOMPOSITION, 1013911

80 C, 59 ppm SUN-Z'

FIGURE 27

TBHP DECOMPOSITION

80 C, 59 ppm SUN - Z', 1013911

TBHP DECOMPOSITION

80 C, 59 ppm SUN - Z', 1013911

FIGURE 28

TBHP DECOMPOSITION, 1013909 80 C, 59 ppm SUN-Z'

FIGURE 29

FIGURE 30

TBHP DECOMPOSITION

80 C, 59 ppm SUN - Z', 1013909

TBHP DECOMPOSITION

80 C, 59 ppm SUN - Z', 1013909

FIGURE 31

TABLE XVII TBHP DECOMPOSITION

TBHP DECOMPOSITION
Effect of temperature
Sun-Z' catalyst @ 80 C

RUN #	CATALYST	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	CAT CONC ppm
2471	BLANK	80	10.0	120	200	0
2478	BLANK	120	15.4	120	200	0
3905	SUN-Z'	80	78.4	335b	200	90
3907	SUN-Z'	120	61.0	135b	200	90
3923a	SUN-Z'	120	30.8	180	200	64
3925a	SUN-Z'	80	79.6	180	200	64
3931a	SUN-Z'	80	86.4	140	0	59
3937a	SUN-Z'	60	89.1	185	0	59
3941a	SUN-Z'	70	88.2	185	0	59

a 8.7 wt % total acetone in the reaction medium.

b Reaction came to halt.

TABLE XVIII TBHP DECOMPOSITION
Effect of added Acetone
Sun-Z' catalyst @ 80 C

RUN #	CAT CONC ppm	% CONV of TBHP	TIME min	PRESSURE psig	TBHP Charge mole %	Acetone Mole % Actual
3905a	90	78.4	335	200	29.24	0
3911b	59	72.4	195	200	31.80	11.6
3925c	59	79.6	180	200	31.68	11.6

a Catalyst (slurried in TBA) heated to 80 C; TBHP added from reservoir, no acetone.

b Catalyst (slurried in TBA) + 1.2 g acetone heated to 80 C; TBHP added from reservoir; 8.7 wt % total acetone.

c Catalyst (slurried in 1.2 g acetone) + TBA heated to 80 C; TBHP added from reservoir; 8.7 wt % total acetone.

TABLE XIX
TBHP DECOMPOSITION
EFFECT OF KETONIC CO-SOLVENT

Run #	Co-Solvent	Catalyst - ppm ^a	Catalyst Stirring Time, Hrs. ^b	cc's O ₂ Evolved in 1st Hr ^c	Time, T _c , to Cessation of O ₂ Evol'n ^d	RO ₂ H Conv. % at T _c ^e	Initial Rate Const.
1005243	None ^f	Sun-Z' - 20	-	170	8	28	
1005252	None ^f	Sun-Z' - 80	-	630	6	83	
1005253	Acetone	Sun-Z' - 19	2	440	2	30	0.034
1005272	Acetone	Sun-Z' - 38	24	1145	2.5	82	0.11
1005254	Acetone	Sun-Z' - 57	2	1320	1	91	
1005269	Acetone	Sun-Z' - 57	84	1365	0.5	96	0.24
1005273	TBA ^g	Sun-Z' - 57	84	1070	4	80	0.08
1005274	MIBK ^h	Sun-Z' - 57	24	1165	1	82	
1005277	Acetone	Sun-Z - 57	144	1345	0.4	95	
1005299	Acetone	Sun-AA' - 57	UNK	820	24	93	
1005297	Acetone	Sun-AA' - 114	168	860	22	94	0.07
1014902	Acetone	Sun-AA' - 228	168	1040	23	98	0.09

a Unless otherwise noted, the catalyst was slurried for the designated time in the designated co-solvent and a slurry added in 3.9 ml acetone to a solution of 13.8 grams TBHP in 18.1 grams of TBA stirred at 80°C. The amount of catalyst was such as to give a solution containing the ppm level indicated in the Table. The solution was stirred at 78°C for the designated time. Oxygen Evolution was followed manometrically and the liquid product profile monitored by standardized glpc.

b Time that the catalyst was stirred in the co-solvent prior to reaction.

c Oxygen evolved (cc's) in the first hour of the reaction.

d Time until all oxygen evolution had ceased.

e $[RO_2H \text{ added} - RO_2H \text{ left}] / RO_2H \text{ added} \times 100$

f Solid catalyst added to hot stirred solution (no acetone) in a boat.

g Catalyst slurried in TBA, tert-butyl alcohol, prior to addition.

h MIBK = Methyl Iso Butyl Ketone

5.1.2.2.3 Effect of Staged Catalyst Addition on SUNZ'

It was postulated that since the catalyst itself is decomposing under the reaction conditions, the catalyst efficiency could be improved by adding the catalyst in small doses. Stagewise addition would also help control the exothermic reaction and rapid oxygen evolution when all catalyst added at one time.

Table XXI shows the effect of stagewise catalyst addition. In the presence of co-solvent acetone, and with stage-wise catalyst addition it was possible to achieve 99 % conversion of TBHP in 1 hour using ~130 ppm catalyst, at 80°C and 1 atmosphere.

5.1.2.2.4 Effect of Feed Drying

Table XXII shows the effect of drying feed components (TBHP, TBA and acetone) on the subsequent decomposition of TBHP. Table XXIII shows the effects of feed drying on reactions run in a glass reactor. Calculated first order rates were superior to runs using wet feed. Table IVB shows that the effects of drying are general for a large number of catalysts.

In experiments 3917, 3921, and 3953, the TBHP was wet, and in experiment 3955, the TBHP added to the reactor had been dried as described in footnote d. In experiment 3921, activated molecular sieves 3A had been added to the reaction mixture. Superior conversion to TBA was obtained when the feed was dried, or when the drying agent was added to the reaction medium.

It is possible to achieve 99% TBHP conversion in 1 hour @ 80°C, 1 atmosphere, dry feed, 18 mole % acetone, and <100 ppm catalyst concentration. It should be noted that the optimum will be dependent on the size of the reactor vessel, at least with respect to dosing effects. We also have not studied the interactions among the different parameters as yet.

5.1.2.3 Catalyst Cost Projections

We are in the process of developing cost estimate for Sun-Z' in commercial quantities. Based on our understanding of the current synthetic routes and yields of various steps, we believe that catalyst cost should be less than 100 \$/lb.

A model to predict catalyst cost per gallon of methyl-t-butylether is presented in Figures 32 and 33. A quantitative equation is derived in Figure 32 to calculate the cost of catalyst as a function of catalyst concentration and the price of catalyst. The catalyst cost is presented graphically in Figure 33. At 100 \$/lb catalyst and 80 ppm catalyst concentration, the final catalyst cost will be 5 c/gal MTBE.

TABLE XX

TBHP DECOMPOSITION

Effect of stage-wise catalyst addition

3917a	SUN-Z'	80	85.3	180	0	59
3931a	SUN-Z'	80	86.4	140	0	59
3933b	SUN-Z'	80	89.5	140	0	59
3935b	SUN-Z'	80	89.9	140	0	59

a All catalyst added @ t=0

b Catalyst added in 3 equal aliquots 10-20 minutes apart

TABLE XXI

TBHP DECOMPOSITION

Effect of drying TBHP

SUN-Z' catalyst @ 80 C

RUN #	CAT CONC ppm	% CONV of TBHP	TIME min	PRESSURE psig	TBHP Charge mole %	Acetone Mole % Actual
3917a	59	85.3	180	0	30.80	11.6
3921b	59	90.7	90	0	31.60	11.6
3953c	89	95.6	60	0	29.18	17.7
3955d	89	99.1	60	0	29.18	17.7

a 5.4 g WET TBHP added to the reactor; the reactor contained catalyst (slurried in acetone) and TBA @ 80 C.

b 5.4 g WET TBHP added to the reactor; the reactor contained catalyst (slurried in acetone) and TBA with 2 g activated molecular sieves (3A) @ 80 C.

c 5.4 g WET TBHP, 1.0 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots.

d 5.4 g TBHP (dried using 3A mol sieves), 1.0 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots.

TABLE XXII
TBHP DECOMPOSITION
EFFECT OF WATER REMOVAL

<u>Run #</u>	<u>Catalyst - ppm</u>	<u>Dry/ Wet^b</u>	<u>Catalyst Stirring Time, Hrs.^c</u>	<u>cc's O₂ Evolved in 1st Hr^d</u>	<u>Time, T_c, to Cessation of O₂ Evol'n^e</u>	<u>RO₂H Conv. % at T_c^f</u>	<u>Initial Rate Const.</u>
1005269	Sun-Z' - 57	Wet	84	1365	0.5	96	0.24
1014928	Sun-Z' - 57	Dry	144	1440	0.1	97	>0.49
1015299	Sun-AA' - 57	Wet	144	820	24	93	0.05
1014930	Sun-AA' - 57	Dry	168	1200	<17	94	0.12
1014944	Sun-AB' - 19	Wet	g	1160	3	NA	0.17
1014940	Sun-AB' - 19	Dry	g	1340	1	NA	0.33

a Same as footnote a, Table 1.

b WET = TBA as purchased from Aldrich (0.05%) TBHP as purchased from Aldrich (90%, 5 wt% H₂O), acetone as purchased from Fisher (0.30%).
DRY = TBA, TBHP and acetone dried over freshly activated 3A mole sieves before use.

c Same as footnote b, Table 1.

d Same as footnote c, Table 1.

e Same as footnote d, Table 1.

f Same as footnote e, Table 1.

g Solid catalyst added to reactor at 80°C.

TABLE XXIII
TBHP DECOMPOSITION
EFFECTS OF WATER REMOVAL

<u>Run #</u>	<u>Catalyst</u>	<u>Dry/ Wet^b</u>	<u>CC's O₂ Evolved in 1st Hr^c</u>	<u>Time, T_c, to Cessation of O₂ Evol'n^d</u>	<u>RO₂H Conv. % at T_c</u>	<u>Initial Rate Const.</u>
1014926	Sun-X	Dry	1380	1.5	95	0.27
1005224	Sun-X	Wet	1280	2	93	0.17
1014911	Sun-2	Dry	1140	>1	NA	0.28
1005178	Sun-2	Wet	930	<3	NA	0.03

a The catalyst, 0.6mg, was added to a solution of 13.8 grams TBHP in 18.1 grams TBA stirred at 80°C. The solution was stirred at 80°C for the designated time. Oxygen evolution was followed manometrically and the liquid product profile monitored by standardized glpc.

b Same as footnote b, Table 3.

c Same as footnote c, Table 1.

d Same as footnote d, Table 1.

e Same as footnote e, Table 1.

Figure 32

TBHP DECOMPOSITION

CATALYST COST

Basis of calculation: 1 lb feed, 40 % TBHP/ 60 % TBA

$$W_{tbhp} = 0.4$$

TBHP concentration in feed, wt %

$$W_{tba} = 0.6$$

TBA concentration in feed, wt %

$$Conc_{cat} = 0, 20.. 200$$

Catalyst concentration, ppm of total feed

$$Price_{cat} = 10, 20.. 100$$

Price of catalyst, \$/lb catalyst

mol wts: TBA= 74.12, TBHP= 90.12, MTBE= 88.15

Density of MTBE= 6.19 lb/gal

Combined selectivity of dehydration + etherification=0.95

Gal of MTBE
produced
per lb of feed

$$G_{mtbe} = \left(W_{tbhp} \cdot 0.85 \cdot \frac{74.12}{90.12} + W_{tba} \right) \cdot (0.95) \cdot \left(\frac{88.15}{74.12} \right) \cdot \left(\frac{1}{6.19} \right)$$

$$G_{mtbe} = 0.161$$

gal MTBE / lb feed

Figure 33

TBHP DECOMPOSITION

$$\text{Cost}_{\text{cat}}(\text{Conc}_{\text{cat}}, \text{Price}_{\text{cat}}) := (W_{\text{tbhp}} + W_{\text{tba}}) \cdot \text{Conc}_{\text{cat}} \cdot 0.000001 \cdot \frac{\text{Price}_{\text{cat}}}{G_{\text{mtbe}}} \cdot 100$$

c/gal mtbe

ppm

Conc_{cat} Cost_{cat}(Conc_{cat}, 100)

0	0
20	1.2
40	2.5
60	3.7
80	5
100	6.2
120	7.5
140	8.7
160	10
180	11.2
200	12.5

Cost_{cat}(Conc_{cat}, 100)Cost_{cat}(Conc_{cat}, 80)Cost_{cat}(Conc_{cat}, 60)Cost_{cat}(Conc_{cat}, 40)

CATALYST COST, c/gal MTBE

SUN-Z' is a proprietary catalyst. We have talked to several specialty chemicals suppliers for price quotes on Sun-Z' in commercial quantities. No one currently makes Sun-Z' in commercial quantities. Based on laboratory synthetic procedures and costs of raw materials, the price of Sun-Z' is projected to be ~60-80 \$/lb. Last quarter we had reported a model to calculate cost of the catalyst per gallon of the methyl-t-butylether, MTBE, product. At 50 psig reaction pressure, the catalyst consumption is 103 ppm to achieve target conversion (Table XXVI). This results in catalyst cost of 3.8 to 5.1 c/gal MTBE. This is an order of magnitude improvement from our initial results.

The catalyst consumption can be as low as 50 ppm if the reaction is carried out at atmospheric pressure. The hatched area in Figure 34 shows the range of catalyst cost in c/gal. MTBE over the operating range of interest.

5.1.2.4 Additional Process Development Activities

Further efforts were directed toward the study of the second step of the two step process for isobutane oxidation. The first step is the non-catalytic conversion of isobutane to t-butyl hydroperoxide. The second step is the catalytic decomposition of t-butyl hydroperoxide (TBHP). The catalysts we tested are various Fe(III)-macrocyclic complexes. The main product of oxidation is t-butylalcohol (TBA).

We have conducted the initial evaluation of several different catalysts in a stainless steel reactor @ 80-120°C, 0-200 psig, and 30 mole % TBHP in t-butyl alcohol(TBA). The conversion of TBHP ranged from 60 to 98 mole % in 1 to 3 hrs. @ catalyst concentration of 15-200 ppm. Sun-Z', a proprietary catalyst, was found to be the most cost effective for the decomposition reaction.

We have further focused on studies with the proprietary catalyst, SUN-Z'. SUN-Z' was chosen for further studies because it is highly active and we believe that it can be manufactured in commercial quantities at a reasonable price. The catalyst cost is estimated to be 2-5 c/gal MTBE based on the above performance.

We have found that TBHP decomposition is 99 % complete in 1 hour reaction time @ 80°C and atmospheric pressure. The catalyst requirement is ~50 ppm based on feed weight, when the catalyst is added in small aliquots. Under similar conditions at 50 psig, the catalyst requirement is ~100 ppm. Use of acetone as co-solvent and drying the feed has extremely beneficial effect in reducing catalyst consumption. Potassium acetate buffer also helps improve the efficiency of the catalyst.

TBHP DECOMPOSITION

CATALYST COST

FIGURE 34

A typical experiment (#1014015) involved a reaction of 39.6 wt % TBHP in TBA with acetone co-solvent (9 wt % concentration) @ 80°C, atmospheric pressure and 10 cc/min N₂ sweep flow. TBHP, TBA and co-solvent acetone were heated to 80°C the flow of nitrogen. Once the reaction conditions were stabilized, 0.4 cc of catalyst slurry in cosolvent acetone was injected in the reactor. Gas output is followed and O₂ evolution is determined by difference of out and in flows. Two more catalyst slurry injections were made at 15 and 30 minutes respectively. The total catalyst addition was 51 ppm based on the total liquid in the reactor. The reaction was shut down after 1 hour by rapid cooling.

The final product from experiment #1014015 was analyzed by gas chromatography. Conversion of TBHP was 93.6% in 60 minutes. The major reaction product was TBA, with acetone and di-t-butylperoxide being by-products. The selectivity for TBA is typically >85 %.

5.1.2.4.1 Effect of Catalyst Concentration

Our target is to achieve >98 % (preferably 99 %) conversion of TBHP in 1 hour with economical catalyst consumption. A number of experiments were carried out to determine minimum catalyst needed to achieve the desired performance. Some of the results are summarized in Table XXIV. We have previously shown (1st quarter 1994 report) that superior performance is obtained by drying TBHP with 3A molecular sieves, and by using acetone co-solvent. All of these experiments were conducted with dried TBHP and in the presence of acetone. Also, the catalyst itself is decomposing during this reaction; hence, catalyst is added in 3 aliquots to minimize catalyst consumption.

As seen from the data in Table XXIV, TBHP conversion increases with more added catalyst; 99% conversion is achieved with 77 ppm catalyst at 80°C and 1 atmosphere pressure.

5.1.2.4.2 Effect of Pressure

Commercially, it is desirable to operate reactors under some nominal pressure. From our preliminary experiments reported in 4th quarter '93 and 1st quarter '94, we know that catalyst decomposition is more rapid at higher reaction pressures. A number of experiments were conducted at 50 psig to determine minimum catalyst consumption for achieving target performance. Important results are summarized in Table XXV. As seen from the results, we need almost 70% more catalyst @ 50 psig to achieve the target performance.

5.1.2.4.3 Effect of Buffer (Potassium Acetate)

It is known in the literature that addition of buffer improves efficiency of the catalyst. A number of experiments were conducted to study this effect. Table XXVI summarizes important results. Addition of 0.011 moles/l of potassium acetate helps achieve 22% higher conversion with 9 ppm of catalyst. The catalyst consumption to achieve our target performance is reduced by almost 1/3 at atmospheric pressure as well as at 50 psig.

TABLE XXIV

TBHP DECOMPOSITION
Effect of catalyst concentration
Sun-Z' catalyst @ 80 C

RUN #	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	Acetone Mole % Actual	N2 Sweep	CATALYST ppm ACE-FREE
4015	80	93.6	60	0	17.7	N	51
4017	80	93.5	60	0	17.7	N	51
4019	80	97.1	60	0	19.4	N	64
4023	80	99.0	60	0	21.1	N	77

5.4 g TBHP (dried using 3A mol sieves), 1.0 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots.

TABLE XXV
TBHP DECOMPOSITION
 Effect of reaction pressure
 Sun-Z' catalyst @ 80 C

RUN #	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	Acetone Mole % Actual	N2 Sweep	CATALYST ppm <u>ACE-FREE</u>
4023	80	99.0	60	0	21.1	N	77
4021	80	97.4	60	50	24.2	Y (P)	103
4025	80	98.6	60	50	27.2	Y (P)	128

5.4 g TBHP (dried using 3A mol sieves), 1.0 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots.

TABLE XXVI

TBHP DECOMPOSITION
Effect of Potassium acetate buffer
Sun-Z' catalyst @ 80 C

RUN #	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	Acetone Mole % Actual	N2 Sweep	CATALYST ppm ACE-FREE
4031a	80	44.3	60	0	14.0	N	9
4037b	80	54.0	60	0	14.0	N	9
4023a	80	99.0	60	0	21.1	N	77
4049b	80	99.4	60	0	17.7	N	51
4021a	80	97.4	60	50	24.2	Y (P)	103
4057b	80	99.5	60	50	24.2	Y (P)	103

5.4 g TBHP (dried using 3A mol sieves), 1.0 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots in 4023, 4049, 4021 and 4057.

a Without buffer

b With potassium acetate buffer (0.011 moles/l)

5.1.2.4.4 Effect of Co-Solvent

We have shown that co-solvents such as acetone help achieve better utilization of the catalyst. To quantify this effect further, several experiments were carried out with low catalyst concentration (and hence low TBHP conversion). This data are summarized in Table XXVII. A small amount of acetone is always used to dissolve/slurry the catalyst. As can be seen, the higher the amount of acetone, the greater the conversion of TBHP, and hence the least catalyst consumption (operating costs). Commercially, one would like to use the least amount of acetone co-solvent as it requires larger reactors and separation trains (more capital cost) to achieve target performance. These data will be used at appropriate time to optimize acetone concentration for the best economics (capital costs vs operating costs).

5.1.2.4.5 Effect of Feed Drying

In past quarterly reports we showed the effect of treatment of the hydrocarbon feed with drying agents such as 3A mole sieves prior to converting TBHP to TBA. We found that with all of the electron-deficient macrocyclic catalysts, this treatment vastly enhanced reaction rates. We have now found that this treatment also greatly enhanced this reaction even with both macrocyclic and non-macrocyclic complexes that do not bear electron-withdrawing groups. Relatively inexpensive catalysts can now be used to rapidly convert TBHP to TBA if the feed is properly pre-treated. Table XXVIII shows the effects of feed treatment on conversion of TBHP to TBA using simple ironphthalocyanine complexes without electron withdrawing groups as catalysts.

5.1.2.5 Catalyst Development Nitroporphines and Halophthalocyanine

P. E. Ellis, Jr., J. E. Lyons and S. N. Shaikh

We continue to prepare and test two novel catalyst types for both the one-step and two-step processes for converting TBHP to TBA: a) metallonitroporphines and b) soluble metallophthalocyanines. As we have discussed, the reason for the study of the nitroporphine complexes is that the nitro group is among the most electron-withdrawing of all substituents and electron withdrawal on the porphyrin ring can be directly correlated with catalytic activity of metalloporphyrin complexes, both for direct oxidation and hydroperoxide conversion to alcohols. Metallophthalocyanine complexes with electron withdrawing groups are also reaction time (Run # 1017053). However, the initial pseudo first order rate constant was never greater than 0.03 /h, which is about one quarter of that observed with our best catalyst $\text{Fe}[\text{PPF}_{20}\text{Cl}_8]\text{OH}$ catalyst.

A number of experiments were conducted using catalysts CAT-X and CAT-X'. The results are summarized in Table XXIX. At 1 atm pressure, 98 % of the TBHP was decomposed in 1 hr using 43 ppm of CAT-X' (RUN # 1017119). When the reaction pressure was 50 psig, 128 ppm of CAT-X' was required to achieve 98.6 % conversion of TBHP. (RUN # 101729).

TABLE XXVII
TBHP DECOMPOSITION
 Effect of acetone (low conversion)
 Sun-Z' catalyst @ 80 C

RUN #	TEMP deg C	% CONV of TBHP	TIME min	PRESSURE psig	Acetone Mole % Actual	N2 Sweep	CATALYST ppm ACE-FREE
4072	80	39.2	60	0	5.0	N	9
4080	80	44.1	60	0	14.0	N	9
4078	80	54.7	60	0	21.4	N	9
4031	80	44.3	60	0	14.0	N	9

5.4 g TBHP (dried using 3A mol sieves), 0-2 g acetone and 7.2 g TBA heated to 80 C in a reactor; catalyst added as acetone slurry in 3 aliquots

TABLE XXVIII
EFFECT OF FEED DRYING ON
CATALYTIC DECOMPOSITION OF TBHP^a

<u>Run #</u>	<u>Date</u>	<u>CATALYST INFORMATION</u>				<u>State^b</u>	<u>Evolved O₂, psi</u>	<u>Time (Min) To O₂ Cessation</u>	<u>TBHP Conv., % After 60 Min.</u>
		<u>Complex</u>	<u>Sample #</u>	<u>mg</u>	<u>ppm</u>				
1014984	5/3	Fe(Pc)Cl	Aldrich	1.80	56.4	WET	1280	52	86
1014985	5/4	Fe(Pc)Cl	Aldrich	1.80	56.4	DRY	1505	7	96
1014996	5/24	Fe(Pc)	Aldrich	1.80	56.4	WET	785	39	49
1014988	5/9	Fe(Pc)	Aldrich	1.80	56.4	DRY	1400	14	92

a) The catalyst, slurried in acetone, was added to a stirred solution of TBA, 18.1g, and TBHP, 13.8g at 80°C. The composition of the catalyst slurry is 3 mg catalyst in 5g acetone. The slurry is prepared by stirring for several days. Oxygen evolution is measured manometrically. Liquid products are analyzed by glpc after one hour.

b) WET = All reagents used as purchased without drying.

DRY = All reagents (TBA, TBHP, acetone) dried over 3A mole sieves for several days prior to use.

TABLE XXIX

TBHP DECOMPOSITION IN STAINLESS STEEL REACTOR
80 C, 40 wt % TBHP + 7.4 wt % acetone in TBA

RUN #	CATALYST	WATER CONC wt %	PRES., psig	CATALYST ppm acetone-free	% CONV		REMARKS
						of TBHP	
7119	CAT-X'	1.8	0	43		98.2	
7129	CAT-X'	1.8	50	128		98.6	
7150	CAT-X	1.8	50	128		92.3	
7152	CAT-X	1.8	50	193		95.4	
7154	CAT-X	1.8	50	128		95.3	250 mg Kacetate added

catalyst added in acetone slurry in 3 aliquats at 0, 7 and 14 min

With 128 ppm of CAT-X @ 50 psig, TBHP conversion was only 92.3 % (#101750), suggesting that it is less active than CAT-X'. Increasing the CAT-X concentration to 193 ppm resulted in 95.4 % conversion of TBHP, still short of our target. Alternatively, adding potassium acetate buffer at 0.18 % level along with 128 ppm CAT-X resulted in 95.3 % conversion at 50 psig reaction pressure. Although the catalyst amounts needed to achieve 98+ % TBHP conversion have not been optimized with buffer concentrations and drying of feed, these are the same trends reported with SUN-Z' in the 2nd quarterly report in 1994. It can be concluded that it is possible to achieve 98+ % TBHP conversion with less than 50 ppm catalyst (CAT-X') @ atmospheric pressure, and with <200 ppm catalyst (CAT-X) @ 50 psig.

The cost of CAT-X and CAT-X' is estimated to be between 10 and 15 \$/lb. Thus, the catalyst cost for the desired performance can be 0.5-1.5 c/gal MTBE from the economic model that was presented in the 2nd quarterly report of 1994.

5.1.2.6 Effect of Feed Drying with Cat-X

Several experiments were conducted to examine the effect of feed drying on decomposition activity of CAT-X. In all of these experiments, a single dose of catalyst slurried in acetone was added at the start of the reaction. TBA and Acetone were always dried with 3A molecular sieves. TBHP was either undried, once dried with molecular sieves, or twice dried with molecular sieves. Drying with molecular sieves was standardized as contacting TBHP with 50 % by wt of activated 3A sieves for 3 days and then decanting the TBHP. The same procedure is repeated one more time to prepare twice dried TBHP.

The results of the experiments are summarized in Table XXX. As in the case with SUN-Z', we find that drying of TBHP improves activity of the catalyst, and the more dried the feed, the higher the activity.

SUN-Z' is a proprietary catalyst.

TABLE XXX

TBHP DECOMPOSITION IN STAINLESS STEEL REACTOR
80 C, 40 wt % TBHP + 7.4 wt % acetone in TBA

RUN #	CATALYST	WATER CONC wt %	PRES., psig	CATALYST ppm acetone-free	% CONV of TBHP	REMARKS
7115	CAT-X	3.8	0	9	23.0	
7134	CAT-X	3.8	0	9	19.9	
7148	CAT-X	3.8	0	9	38.2	25 mg Kacetate added
7156	CAT-X	3.8	0	9	40.5	2 g activated 3A mole sieves added
7109	CAT-X	1.8	0	9	56.8	Once dried TBHP
7136	CAT-X	1.8	0	9	53.5	Once dried TBHP
7142	CAT-X	0.05	0	9	63.8	Twice dried TBHP
7144	CAT-X	0.33	0	9	61.9	Twice dried TBHP + 0.04 g water