Mason & Hanger-
Silas Mason Co., Inc.

ENGINEERS AND CONTRACTORS

SINCE 1827

Pantex Plant

HE FORMULATION

SANLS 712-003 & 008

A. G. Osborn

April, May, June 1970

DEVELOPMENT DIVISION

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
B

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

HE FORMULATION

A. G. Osborn

April, May, June 1970
SANLS 712-003 & 008

ABSTRACT

Micronized PETN was subjected to temperatures above 212°F for time periods of 2 to 8 hours to determine if the previous 300-hour cycle could be shortened. It appears that PETN is effectively stabilized after 8 hours at 240°F.

Other PETN samples were treated with wetting agents and also subjected to 240°F for 8 hours. Seven of the twelve treated samples showed a substantial increase in stabilized surface area with the highest being 16,850 cm²/g S₀^P after being washed with Stein Hall's Jaguar J2S1. Untreated surface area was 5,000 cm²/g S₀^P.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCUSSION

S_0^P Stabilization at $> 100^\circ\text{C}$

In the past, a few PETN samples which were heated at or near 240°F for several hours exhibited a high degree of surface area stability, suggesting the shortening of the long 300-hour cycle at 212°F . At that time some questions arose concerning the accuracy and cycling of the ovens. Therefore, the ovens were calibrated and steam control valve positioners installed to minimize cycling and enhance response. Control is now very fine, with cycling undetectable on the circular chart recorders. With this improvement, a much more comprehensive heat aging study was initiated.

The study consisted of heating samples at temperatures from 220°F to 240°F in 5° increments for 2, 4, 6, and 8 hours at each temperature. This makes a total of 20 different combinations of time and temperature. To verify or to determine the extent of change or stabilization, samples were withdrawn after completing each condition and further subjected to a 300 hour/ 212°F test cycle. Results, along with a control sample, are given in Table I and plotted in Figs. 1 through 4.

Figs. 1, 2, and 3 show the results of the high temperature aging plus the post-aging 300-hour/ 212°F heat cycle for each condition. The control sample heated only at 212°F for 300 hours is also shown in Fig. 3. (In Figs. 1, 2, and 3, except for the control sample, the upper portions of the curves from 7,500 to 18,200 cm^2/g were omitted.) As shown by the flatter curve, Fig. 3, the most stable sample was obtained at 240°F for 8 hours. In Fig. 4, upper plot, the surface areas obtained from the high temperature short cycles are again presented, collectively for comparison. The lower plot, Fig. 4, is very interesting; it is a plot of the 300-hour 212°F test cycle and depicts the $220^\circ\text{F}/8$ hours sample starting at a higher surface area than the $240^\circ\text{F}/8$ hour sample, yet

Fig. 1

Fig. 2

Fig. 3

Fig. 4

Exposure at 212°F After Pre-aging at Higher Temperature

finishing at a lower surface area. The differences in surface areas are small—on the order of 300 to 700 cm²/g—but the pattern may be observed in almost every case, as may be seen in Table I and by comparing samples heated for the same time periods: the sample initially subjected to the higher temperature starts at a lower surface area, yet finishes higher. That is true at any heating time, whether 2, 4, 6, or 8 hours, suggesting that the higher the temperature (within limits of course) the higher the final stabilized surface area. This idea is also supported by the control sample data. It was heated at the lowest temperature, 212°F, and stabilized at the lowest surface area, 3650 cm²/g S_0^P .

Fig. 5 contains photomicrographs of the stabilized control sample, sample heated at 8 hours/240°F, and, then at 8 hours/240°F plus 300/212°F.

Effect of Wetting Agents on S_0^P Stabilization

A study of the stabilizing effect of wetting agents is also being conducted. Twelve have been tried and eight others have been received. The presence of certain types of large molecules on the crystal surface should interfere with the surface activity resulting in less growth and crystal change. Work conducted in the past with sodium dodecyl sulfate and sodium hexadecyl sulfate suggested that stabilization is more than a possibility, well within the reach of reality. The survey this quarter year is simply for the purpose of picking the most promising prospects for further work. For each agent, a sample of approximately 200 g of Micronized PETN was collected in the centrifuge and subsequently washed with three gallons of water containing 200 ppm of wetting agent,

Table I

PETN Surface Area (S_0^P cm²/g)
Stabilization Study 0145-304M-01

Control Sample Heated @ 212°F						
Initial S_0^P	8 Hrs.	24 Hrs.	100 Hrs.	168 Hrs.	200 Hrs.	300 Hrs.
18250	6900	5100	4100	3700	3700	3650

220°F		212°F		
		119 Hrs.	199 Hrs.	300 Hrs.
2 Hrs.	7400	4700	4400	4050
4 Hrs.	6050	4600	4300	4000
6 Hrs.	5450	4550	4250	4000
8 Hrs.	5300	4400	4100	4000
225°F				
2 Hrs.	6800	4700	4450	4200
4 Hrs.	5700	4550	4400	4200
6 Hrs.	5250	4600	4250	4250
8 Hrs.	5000	4450	4250	4050
230°F				
2 Hrs.	5900	4900	4750	4450
4 Hrs.	5350	4600	4600	4450
6 Hrs.	4900	4450	4500	4300
8 Hrs.	4700	4350	4300	4150
235°F				
2 Hrs.	5650	5000	4900	4500
4 Hrs.	5050	4800	4600	4450
6 Hrs.	4700	4600	4450	4250
8 Hrs.	4600	4400	4250	4100
240°F				
2 Hrs.	5300	4850	4850	4550
4 Hrs.	5000	4650	4800	4500
6 Hrs.	4700	4650	4500	4300
8 Hrs.	4600	4450	4500	4300

PETN 0145-304M-01
8 Hours @ 240°F

1000X
4,600 cm²/g S₀^P

PETN 0145-304M-01
8 Hours @ 240°F
Plus
300 Hours @ 212°F

1000X
4,300 cm²/g S₀^P

PETN 0145-304M-01 1000X
Control - 300 Hours @ 212°F
3,650 cm²/g S₀^P

Fig. 5

PETN 0174 304M-1C 1000X
19,650 cm²/g S₀^P

PETN 0174 304M-1C 1000X
8 Hours @ 240°F 5,000 cm²/g S₀^P

PETN 0174 304M-JB 1000X
24,300 cm²/g S₀^P

PETN 0174-304M-JB 1000X
8 Hours @ 240°F 11,600 cm²/g S₀^P

Fig. 6

PETN 174-304M-J251 1000X
23,400 cm²/g S₀^P

PETN 0174-304M-J251 1000X
8 Hours @ 240°F 16,850 cm²/g S₀^P

PETN 0174-304M-X100 1000X
17,000 cm²/g

PETN 0174-304M X-100 1000X
8 Hours @ 240°F 3,850 cm²/g S₀^P

Fig. 7

PETN 0174-304M-705DB
8 Hours @ 240°F

1000X
10,500 cm²/g

PETN 0174-304M-1212A
8 Hours @ 240°F

1000X
9,650 cm²/g

PETN 0174-304M-Plus
8 Hours @ 240°F

1000X
12,200 cm²/g S₀^P

PETN 0174-304M-SHS
8 Hours @ 240°F

1000X
5,850 cm²/g S₀^P

Fig. 8