LA-UR-

Approved for public release,
distribution is unlimited.

97-3667

Title:

SHORT RANGE SPIN CORRELATIONS IN THE
CMR MATERIAL $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$

CONF-970814--

Author(s):

T. M. Kelley, D. N. Argyriou,
R. A. Robinson, H. Nakotte,
J. F. Mitchell, R. Osborn, and
J. D. Jorgensen

Submitted to:

Physica B
(Proceedings of ICNS 97, Toronto,
Canada, August 17-21, 1997)

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *ph*

MASTER

Los Alamos

NATIONAL LABORATORY

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by the University of California for the U.S. Department of Energy under contract W-7405-ENG-36. By acceptance of this article, the publisher recognizes that the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy. The Los Alamos National Laboratory strongly supports academic freedom and a researcher's right to publish; as an institution, however, the Laboratory does not endorse the viewpoint of a publication or guarantee its technical correctness.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

Short Range Spin Correlations in the CMR Material $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$

T. M. Kelley^a, D. N. Argyriou^a, R. A. Robinson^a, H. Nakotte^a,
J. F. Mitchell^b, R. Osborn^b, J. D. Jorgensen^b

a. Manuel Lujan, Jr., Neutron Scattering Center, Los Alamos National Laboratory, Los Alamos, NM 87545, U.S.A.

b. Materials Science Division, Argonne National Laboratory, Argonne, IL 60439 U.S.A.

The $(\text{La}_{1-x}\text{Sr}_x)_2\text{Mn}_3\text{O}_7$ compounds are layered materials that exhibit higher magneto-resistance than the corresponding 3D manganite perovskites. Quasi-elastic neutron scattering on a polycrystalline sample of $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$ shows that the spin fluctuation spectrum of these layered CMR materials is qualitatively similar to those found in the perovskite manganites $(\text{La,Ca})\text{MnO}_3$; their concentration, lifetime, and coherence length increase as T decreases to T_c . Unlike the perovskites we find a lower spin-diffusion constant above T_c of $\sim 5 \text{ meV \AA}^2$.

Keywords: colossal-magneto-resistance, $(\text{La}_{1-x}\text{Sr}_x)_2\text{Mn}_2\text{O}_7$, magnetic polarons

T. M. Kelley, MS H805, Los Alamos National Laboratory, Los Alamos, NM 87545 U.S.A.

e-mail: tmk@lanl.gov

FAX: (505) 665-2676

voice: (505) 665-3768

The close interplay among charge, spin, and lattice degrees of freedom in the colossal magneto-resistive (CMR) manganite oxides is widely believed to play an important role in the mechanism of transport in these itinerant ferromagnets. Among the current models of transport in the three-dimensional magneto-resistive perovskite materials is that magnetic polarons—mobile lattice distortions carrying spin—play a fundamental role, at least above the Curie temperature (T_C).^{1,2} Supporting evidence for this model have been provided recently by DeTeresa, *et al.* from in-field small angle neutron scattering experiments on the perovskite $\text{La}_{2/3}\text{Ca}_{1/3}\text{MnO}_3$.² In this paper we report inelastic neutron scattering measurements from the layered CMR material $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$.

Inelastic neutron scattering data were taken from a 15g, single phase polycrystalline sample of $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$ using the time-of-flight chopper spectrometer PHAROS at MLNSC, Los Alamos National Laboratory. Data were taken at 12 temperatures, ranging from 30 K to 320 K using an incident energy $E_i=12.1$ meV, except for data measured at 115 K where incident energies of 12.1 and 8.1 meV were used to extend the Q-range of the measurement. Neutron powder diffraction data were measured as a function of temperature from 20-300K, using (SEPD) at IPNS at the Argonne National Laboratory. This polycrystalline sample was characterized using a.c. susceptibility and resistivity; a PI-FM transition was observed at 116K.

Fig. 1 shows the spectrum at 115 K and 30 K, with a gaussian fit to each: while there is little statistically significant deviation from the gaussian at 30 K, at 115 K the gaussian is clearly unable to fit the data. The addition of a lorentzian term $L(\epsilon)=\text{BIG}/p(\epsilon^2+\Gamma^2)$ to fit the quasi-elastic component gives a much better fit to the data (ϵ is the energy transfer, B the Bose-Einstein factor, I the integrated intensity, and Γ the half-width at half maximum). This gives an intensity and a lifetime ($\tau = \hbar/\Gamma$) for the spin correlations at each temperature (Fig. 2). The quasi elastic scattering diverges as $Q \rightarrow 0$, suggesting that it is due to ferromagnetic spin-correlations. Similar observation have been made by Lynn *et al.*³ for the three dimensional perovskite manganites.

The intensity of the quasi-elastic scattering increases as the sample is cooled from 322 K to T_C , then decreases below T_C , with similar behavior for the lifetime. Fitting the intensity as a function of Q gives a correlation length of ~ 12 Å at 128 K, while fitting the energy width as a function of Q gives a spin-diffusion constant of ~ 5 meV Å². This value is substantially lower than

the 30 meV $\text{\AA}^2$ measured for $\text{La}_{0.67}\text{Ca}_{0.33}\text{MnO}_3$ ³ and may reflect the effect of reduced dimensionality on the dynamics of spin fluctuations.

Neutron powder diffraction measurements from the same sample used for the inelastic scattering measurements show that a relaxation of the lattice occurs at T_C . For the perovskite materials this has been interpreted as the relaxation of localized lattice distortions from lattice polarons. The close correlation of the spin-dynamics (i.e. the increase of the quasi elastic scattering as $T \rightarrow T_C$), with the relaxation of the lattice suggests that these two phenomena are coupled. This observation is qualitatively similar to results reported by De Teresa *et al.*² for $\text{La}_{2/3}\text{Ca}_{1/3}\text{MnO}_3$. However, magnetic scattering from layered $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$ is complicated by the fact that in two-dimensional magnetic systems critical magnetic fluctuations can be enhanced well above T_C (e.g. K_2CuF_4 ⁴). Work is currently underway to decouple the expected 2-D ferromagnetic fluctuations from any additional signal that may emerge from magnetic polarons.

In conclusion, we observe a quasi-elastic magnetic scattering in $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$, between $0.7 < T_C < 2.8 T_C$. The intensity of the scattering and the lifetime of spin fluctuations increases as T decreases to T_C . This phenomenon correlates strongly with the electronic (insulator-metal) and structural transition at the onset of 3D magnetic ordering.

This work was supported by the U.S. Department of Energy, Basic Energy Sciences-Materials Sciences under contract W-7405-ENG-36 (TMK, DNA, RAR) and W-31-109-ENG-38 (JFM, RO, JDJ).

References

- ¹H. Röder, J. Zang and A. R. Bishop, Phys. Rev. Lett. **76**, 1356 (1996).
- ²J. M. Deteresa, M. R. Ibarra, P. A. Algarabeli, C. Ritter, C. Marquina, J. Blasco, J. Garcia, A. Delmoral and Z. Arnold, Nature **386**, 256 (1997).
- ³J. W. Lynn, R. W. Erwin, J. A. Borchers, Q. Huang, A. Santoro, J.-L. Peng and Z. Y. Li, Phys. Rev. Lett. **76**, 4046 (1996).
- ⁴Kinshiro Hirakawa, Hideki Yoshizawa, John D. Axe, and Gen Shirane, J. Phys. Soc. Japan, **52**, 4220 (1983)

Figure captions:

Fig. 1: Quasi-elastic spectrum from $\text{La}_{1.4}\text{Sr}_{1.6}\text{Mn}_2\text{O}_7$ at 30 K (top) and 115 K (bottom). The data are integrated over the available Q range of ~ 0.15 to $0.45 \text{ \AA}^{-1}$. The solid curves are gaussian fits.

Fig. 2: (a) Intensity of the quasi-elastic component as a function of temperature. (b) Lifetime ($=\hbar/\Gamma$) as a function of temperature. Both the intensity and lifetime were obtained by fitting to the data integrated over the available Q-range of ~ 0.15 to $0.45 \text{ \AA}^{-1}$. (c) Susceptibility and resistivity data from this sample.