UCRL 95703
PREPRINT

GEOCHEMICAL SIMULATION OF DISSOLUTION
OF WEST VALLEY AND DWPf GLASSES
IN J-13 WATER AT 90°C

Carol J. Bruton

Materials Research Society Symposium
Boston, MA
Nov. 30 - Dec. 5, 1987

MASTER

November 1987

Lawrence
Livermore
National
Laboratory

This is a preprint of a paper intended for publication in a journal or proceedings. Since changes may be made before publication, this preprint is made available with the understanding that it will not be cited or reproduced without the permission of the author.

UCRL--96703

DE88 005619

Prepared by Nevada Nuclear Waste Storage Investigations (NNWSI) Project participants as part of the Civilian Radioactive Waste Management Program. The NNWSI Project is managed by the Waste Management Project Office of the U.S. Department of Energy, Nevada Operations Office. NNWSI Project work is sponsored by the Office of Geologic Repositories of the DOE Office of Civilian Radioactive Waste Management.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

8/2/90

GEOCHEMICAL SIMULATION OF DISSOLUTION OF WEST VALLEY AND DWPF GLASSES IN J-13 WATER AT 90°C

Carol J. Bruton

Lawrence Livermore National Laboratory, P.O. Box 808, Livermore, CA 94550

ABSTRACT

Dissolution of West Valley and Defense Waste Product Facility (DWPF) glasses in J-13 water at 90°C at the candidate Yucca Mountain, Nevada repository was simulated using the EQ3/6 computer code package. The objectives of the study were to attempt to predict the concentrations of radionuclides and other glass components in solution resulting from glass dissolution, and to identify potential precipitates that sequester glass components.

Modified projected inventories of 10,000 year-old West Valley and DWPF SRL-165 frit glasses were used as starting glass compositions. J-13 water was considered to be representative of groundwater at Yucca Mountain. A total of 10 grams of each glass was assumed to dissolve congruently into a kilogram of J-13 water in a closed system. No inhibitions to precipitation, except for crystalline SiO_2 polymorphs, were assumed to exist. Radiolysis and materials interactions were not considered.

Simulation results predict that radionuclides and other glass components precipitate predominantly in the form of oxides and hydroxides, together with carbonates, silicates and phosphates. Precipitates appear to be effective in limiting the concentrations of radionuclides and other elements in solution. The general compositional trends in precipitates and solution chemistry are the same in the West Valley and DWPF simulations, except for variations arising from differences in glass chemistry.

Concentrations of elements released from glass increase until the solution reaches saturation with respect to solids that contain these elements. Elemental concentrations are then predicted to remain constant, increase or decrease depending on: 1) whether the reaction between the dominant aqueous species of the element in solution and its precipitate is pH and/or Eh-dependent; 2) whether the species distribution of the element in solution changes significantly in response to changes in pH, Eh, or other factors; and 3) the competition with other phases for elements required to form the precipitate. pH increases from 7.3 to 9.8 and from 7.2 to 10 in the West Valley and DWPF simulations, respectively. Eh decreases abruptly from about 0.5 to 0.3 volts after dissolution of 3.4 and 5.8 grams of glass in the West Valley and DWPF simulations, respectively, because of depletion of dissolved oxygen in solution. Complexing of aqueous species has a significant impact on radionuclide concentrations in solution; predicted concentrations of U in solution, for example, are controlled by the presence or absence of P in solution because H_2PO_4 is an extremely effective complexing agent for U.

INTRODUCTION

Geochemical simulations of glass waste form degradation in an aqueous environment are being used to help satisfy Nuclear Regulatory Commission regulation 10 CFR 60 and Environmental Protection Agency 40 CFR 191, which place limits on elemental releases from proposed repositories over time periods of thousands of years and under a variety of conditions. Given appropriate kinetic data for rates of release and other rate-dependent phenomena, geochemical models can be used to predict repository performance over extended time periods and under a variety of scenarios which are other-

wise unattainable in the laboratory. Geochemical models are process-oriented; that is, they simulate and quantify the many interactions that occur in the fluid and between the fluid and waste package, and provide for interactions among competing processes. Geochemical simulations described in this report focus on the behavior of released radionuclides from potential glass waste forms in the candidate Yucca Mountain, Nevada repository. Objectives of this study were to: 1) predict elemental concentrations of radionuclides in solution resulting from glass dissolution; 2) identify controls on solution composition; 3) identify potential precipitates that may limit radionuclide concentrations in solution; and 4) evaluate sufficiency of thermodynamic data base for modeling needs.

GEOCHEMICAL SIMULATION OF WASTE DEGRADATION IN AN AQUEOUS ENVIRONMENT USING THE EQ3/6 CODE PACKAGE

Reaction of West Valley and Defense Waste Product Facility (DWPF) glasses with J-13 groundwater at 90°C was simulated using version 3245 of the EQ3/6 geochemical modeling code package with version 3245R48 of the EQ3/6 thermodynamic data bases. The foundations of the EQ3/6 code are discussed by [1]. Projected 10,000 year inventories of West Valley and DWPF SRL-165 frit glasses obtained from [2] and [3], respectively, were used as the starting glass compositions (Table 1). Elements which were listed in the above references but not contained in the EQ3/6 thermodynamic data base, such as Zr, were not considered in the simulations. Glass was assumed to

Table 1. Projected 10,000 year inventories of West Valley and DWPF glasses [2,3].

WEST VALLEY GLASS				DWPF DP MS-85-141 GLASS			
Element	Oxide	Oxide wt%	Element moles/g	Element	Oxide	Oxide wt%	Element moles/g
Si	SiO ₂	4.58E+01	7.63E-03	Si	SiO ₂	5.41E+01	9.02E-03
Fe	Fe ₂ O ₃	1.25E+01	1.56E-03	Fe	Fe ₂ O ₃	5.92E+00	7.41E-04
Al	Al ₂ O ₃	2.89E+00	5.67E-04	Al	Al ₂ O ₃	9.80E+00	1.92E-03
B	B ₂ O ₃	1.02E+01	2.92E-03	B	B ₂ O ₃	8.28E+00	2.38E-03
Na	Na ₂ O	1.12E+01	3.60E-03	Na	Na ₂ O	1.08E+01	3.50E-03
Li	Li ₂ O	2.31E+00	2.08E-03	Li	Li ₂ O	4.81E+00	3.23E-03
U	UO ₂	5.73E-01	2.12E-05	U	UO ₂	2.03E+00	7.53E-05
Co	CoO	2.08E-04	2.73E-08	Co	CoO	-----	-----
Cr	Cr ₂ O ₃	3.19E-01	4.18E-05	Cr	Cr ₂ O ₃	-----	-----
Cu	CuO	1.02E-04	1.29E-08	Cu	CuO	-----	-----
Mn	MnO ₂	1.34E+00	1.54E-04	Mn	MnO ₂	1.87E+00	2.15E-04
Ni	NiO	3.44E-01	4.59E-05	Ni	NiO	9.08E-01	1.22E-04
Ru	RuO ₂	7.75E-02	5.83E-06	Ru	RuO ₂	-----	-----
Zn	ZnO	1.02E-03	1.26E-07	Zn	ZnO	-----	-----
Ba	BaO	5.52E-02	3.60E-06	Ba	BaO	4.48E-23	2.93E-27
Ca	CaO	6.14E-01	1.05E-04	Ca	CaO	2.36E-01	4.21E-05
Cs	Cs ₂ O	8.43E-02	5.98E-06	Cs	Cs ₂ O	6.90E-02	4.90E-06
K	K ₂ O	3.66E+00	7.15E-04	K	K ₂ O	-----	-----
Mg	MgO	1.34E+02	3.32E-04	Mg	MgO	9.86E-01	2.45E-04
Sr	SrO	2.75E-02	2.66E-06	Sr	SrO	4.21E-02	4.06E-06
P	P ₂ O ₅	2.57E+00	3.63E-04	P	P ₂ O ₅	-----	-----
S	SO ₂	2.21E-01	2.77E-05	S	SO ₂	-----	-----
Th	ThO ₂	3.66E+00	1.39E-04	Th	ThO ₂	2.78E-04	1.05E-08
Eu	Eu ₂ O ₃	1.43E-03	8.15E-08	Eu	Eu ₂ O ₃	-----	-----
C	CO ₂	1.00E-04	2.28E-08	C	CO ₂	-----	-----
Se	SeO ₂	1.48E-03	1.33E-07	Se	SeO ₂	1.31E-03	1.18E-07
Tc	Tc ₂ O ₇	3.03E-01	1.97E-05	Tc	Tc ₂ O ₇	1.13E-01	7.35E-06
Sn	Sn ₂ O ₂	3.41E-03	2.26E-07	Sn	SnO ₂	4.09E-03	2.71E-07
I	I ₂	4.28E-03	3.38E-07	I	I ₂	-----	-----
Pb	PbO ₂	1.70E-09	7.13E-14	Pb	PbO ₂	5.98E-08	2.50E-12
Ra	RaO	1.17E-07	4.84E-12	Ra	RaO	4.06E-06	1.67E-10
Np	NpO ₂	9.18E-03	3.41E-07	Np	NpO ₂	2.02E-03	7.50E-08
Pu	PuO ₂	6.85E-03	2.50E-07	Pu	PuO ₂	1.15E-02	4.21E-07
Am	AmO ₂	1.88E-03	6.85E-08	Am	AmO ₂	1.54E-05	5.59E-10

dissolve congruently in a closed system into a static, 1 kilogram mass of water that accumulated in the waste canister. J-13 water, whose composition is given in Table 2, was considered to be representative of groundwater in the proposed Yucca Mountain repository [4]. The initial fugacity of oxygen in J-13 water was assumed to equal 0.2 bars to reflect equilibrium with the atmosphere in the unsaturated zone.

Reaction between glass and J-13 water was calculated as a function of the mass of dissolved glass per kilogram of J-13 water. A total of 10 grams of each glass, which corresponds to release of 0.6 parts in 10^5 of the waste inventory, was assumed to dissolve congruently into a kilogram of J-13 water. An explicit kinetic model of glass degradation was not used pending testing of the adequacy of available models. The mass of dissolved glass per kilogram of water does not imply that the entire mass of elements released from glass dissolution exists as dissolved species. Many elements precipitate from solution as part of secondary phases. Materials interactions and radiolysis were not considered in the simulations.

Over 550 solids were considered by the code as potential precipitates. No inhibitions to precipitation were assumed to exist, except for crystalline SiO_2 polymorphs, as discussed below. Modeling with EQ3/6 contrasts with modeling with PHREEQE [5] which requires the user to identify precipitating phases. Prediction of system performance under physical and chemical conditions which have not been matched in the laboratory or for time periods unattainable in the laboratory requires use of a code such as EQ3/6 which need not rely on user input to specify precipitates. Constraints on precipitates observed in the laboratory can be accounted for in EQ3/6 when necessary, however. Quartz and all other silica polymorphs except for amorphous silica, for example, were not allowed to precipitate in the simulations described in this paper to reflect observed inhibitions to precipitation of crystalline SiO_2 polymorphs at 90°C [6].

Solid solutions were modeled assuming ideal, molecular mixing among end member components. Clay mineral solid solutions were represented by dioctahedral and trioctahedral smectites [7]. Colloid formation and sequestering of radionuclides as trace components of solid solutions or as sorbed species were not considered.

Results of the modeling are being used to help guide expansion and refinement of the EQ3/6 thermodynamic database. Thermodynamic data for radionuclide-bearing phases and aqueous species have been obtained from many different sources and may be incomplete. Much of the data had to be extrapolated to 90°C. Simulations described in this report should be viewed as a first step in using geochemical models to simulate repository behavior because simulation results are affected significantly by the accuracy and completeness of the thermodynamic database. At this stage in the simulations, the absolute values of elemental concentrations and other parameters

Table 2. Average fluid analysis of LLNL laboratory supply of J-13 water [4].

Component	Concentration (mg/l)
Li	0.042
Na	43.9
K	5.11
Ca	12.5
Mg	1.92
Si	0.035
Al	0.012
Fe	0.006
Si	27.0
NO_3	9.6
F	2.2
Cl	6.9
HCO_3	125.3
SO_4	18.7
pH	7.6

are not as important as identifying potential controls on solution composition. Critical interactions in the fluid and between the fluid and precipitates must be identified and used to guide future research. Predicted precipitates represent the general mineral group and/or chemical composition of potential precipitates, rather than their exact identity. Kinetic inhibitions to the precipitation of crystalline phases may result in the formation of metastable, amorphous precipitates and other phases rather than predicted crystalline precipitates. The simulations yield, nonetheless, a general guide to the chemistry of potential precipitates and reacted J-13 water through time. Data base expansion and refinement, carried out in concert with experimental investigations and theoretical simulations, will allow improved predictions of repository performance over time.

REACTION OF WEST VALLEY GLASS WITH J-13 WATER AT 90°C

Solid Precipitates

The sequence and relative masses of predicted solid precipitates in the West Valley glass simulation are shown in Figure 1 as a function of the logarithm of the mass of dissolved glass per kilogram of J-13 water. The bars represent the stability range of each solid. The beginning of the bar signifies precipitation of the solid, whereas the end of the bar denotes complete dissolution of the solid. The width of the bar represents the mole percentage of the precipitate in the solid phase assemblage at each step in reaction progress. Mole percentages of less than about 5% are designated by the same reference line widths.

Raising the temperature of J-13 water from ambient conditions to 90°C prior to glass dissolution results in predicted precipitation of small amounts of talc, dioctahedral and trioctahedral smectite, and a calcite solid solution. The dioctahedral smectite solid solution is nontronitic, with Ca and Mg dominating the exchange site and Fe occupying the octahedral site. The trioctahedral smectite is saponitic with Ca and Mg dominating the exchange position and Mg occupying the octahedral site. The CaCO_3 component dominates the MgCO_3 component in the calcite solid solution. Precipitation of these minerals reflects the control of the Yucca Mountain tuff on the composition of J-13 water and the effect of temperatures greater than ambient on solid phase equilibria.

Figure 1. Predicted paragenetic sequence of secondary solid phases formed during dissolution of West Valley glass in J-13 water at 90°C (see text).

Addition of 10^{-12} moles of Co, Mn, P, Pu, Th and Ru to J-13 water through simulated glass dissolution causes precipitation of $\text{Co}(\text{FeO}_2)_2$, pyrolusite (MnO_2), fluorapatite ($\text{Ca}_5(\text{PO}_4)_3\text{F}(\text{c})$), $\text{PuO}_2(\text{c})$, thorianite (ThO_2) and $\text{RuO}_2(\text{s})$, respectively. The designation 'c' refers to a crystalline phase, whereas 's' is appended to the formula of some solids, which are not necessarily crystalline, to differentiate them from uncharged aqueous species in the data base. Solids that are minerals are named. Predicted early oxide precipitates are reasonable analogues to amorphous phases that have been observed experimentally [8]. They may, alternately, be artifacts that arise because no provision was made for the incorporation of the elements as trace components of solid solutions.

Further dissolution of glass in J-13 water results in predicted precipitation of additional solids that sequester radionuclides and other glass components. The sequence of precipitates includes: Ni_2SiO_4 , witherite (BaCO_3), petalite ($\text{Li}_2\text{Al}_2\text{Si}_2\text{O}_{10}$), $\text{Am}(\text{OH})\text{CO}_3(\text{c})$, $\text{Eu}(\text{OH})_3$, haiweeite ($\text{Ca}(\text{UO}_2)_2\text{Si}_6\text{O}_{15}\cdot 5\text{H}_2\text{O}$), zincite (ZnO), SnO_2 , tenorite (CuO), NpO_2 , hydroxyapatite ($\text{Ca}_5(\text{PO}_4)_3(\text{OH})(\text{c})$), B_2O_3 and bixbyite (Mn_2O_3). No precipitates containing the elements Cr, Cs, Se, Tc, Pb and Ra as primary components are predicted to form during dissolution of 10 grams of glass into 1 kg of J-13 water. Pollucite, which is not in the current EQ3/6 data base, has precipitated during experiments [9] to sequester Cs. Solid precipitates sequestering radionuclides and other glass components in the simulations tend to be oxides or hydroxides, together with carbonates, silicates and phosphates. The dominance of various oxides as secondary precipitates may be an artifact of the relatively complete representation of oxides and hydroxides of radionuclides in the thermodynamic data base relative to the sparse data set for other solids containing radionuclides. Further data base work is required to include provision for all potential radionuclide-bearing solids.

As glass dissolves during the simulation, the calcite solid solution becomes increasingly Sr-rich, until the SrCO_3 component forms 96 mole % of the solid solution. The smectites become increasingly enriched in Na and K on the exchange site, and the saponites dissolve because of competition with talc for Mg in the system. Tremolite precipitates for a short while as an additional sink for Mg in the system.

Solution Chemistry

Predicted concentrations of selected elements, expressed as the logarithm of elemental molality, are shown in Figures 2 and 3 as a function of the logarithm of the mass of dissolved glass per kilogram of J-13 water. Values of pH and Eh during reaction are shown in Figure 4. Tc increases linearly in concentration to $10^{-3.7}$ M (18.7 mg/kg) in direct correspondence to its rate of release from glass because it is not sequestered by any precipitate. The concentration of Th in solution is limited at the start of the simulation by the precipitation of thorianite, whereas the concentration of Sn increases linearly in solution until SnO_2 precipitates. The concentrations of Th and Sn are then maintained at $10^{-13.9}$ and $10^{-6.9}$ M (3×10^{-9} and 0.015 mg/kg). Precipitation of $\text{Am}(\text{OH})\text{CO}_3(\text{c})$, $\text{Eu}(\text{OH})_3$ and Ni_2SiO_4 causes concentrations of Am, Eu and Ni to maximize at $10^{-8.1}$, 10^{-8} and $10^{-7.7}$ M, and then decrease. Their concentrations decrease, rather than remaining constant, because of the changing chemical characteristics of the solution. pH, for example, increases steadily throughout the simulation. Reactions between the dominant aqueous species of Sn and Th and their precipitates are pH-independent, whereas reactions for Am, Eu and Ni are pH-dependent (e.g. $\text{H}^+ + \text{Eu}(\text{OH})_3 \rightleftharpoons \text{Eu}(\text{OH})_2^+ + \text{H}_2\text{O}$). Increasing pH causes the concentration of elements involved in a pH-sensitive reaction with a solid to change accordingly. Solution speciation must be known accurately in order to predict elemental concentrations in solution.

Figure 2. Predicted concentrations of B, Ca, Li, Np, P, Si, Sn, Sr and U in solution, expressed as the logarithm of molality, resulting from dissolution of West Valley glass in J-13 water at 90°C.

Figure 3. Predicted concentrations of Am, Co, Eu, Mn, Ni, Pu, Ru and Th in solution, expressed as the logarithm of molality, resulting from dissolution of West Valley glass in J-13 water at 50°C.

B, Co, Li, P, Si and U concentrations increase through the simulation despite the precipitation of solids, which are able to sequester only a portion of the released elements. Precipitation of solids is sometimes not limited by the availability of the element of interest, but by the availability of other elements contained in the solid. For example, precipitation of the Li-bearing aluminosilicate, petalite, is limited by the availability of Al rather than Li or Si. pH and other characteristics of the solution as a whole that tend to "buffer" system response may also act to limit precipitation. After dissolution of 10 grams of glass in 1 kg of J-13 water, elemental concentrations equal: $10^{-1.6}$ m (259 mg/kg) B; 10^{-9} m Co; $10^{-1.8}$ m (120 mg/kg) Li; $10^{-2.6}$ m (87 mg/kg) P; $10^{-1.5}$ m (869 mg/kg) Si; and $10^{-3.7}$ m (49 mg/kg) U. The complex $\text{UO}_2(\text{H}_2\text{PO}_4)_2$ accounts for nearly 100% of U in the aqueous phase.

Concentrations of Mn, Np, Pu and Ru in solution are affected greatly by a drop in Eh from 0.5 to 0.3 v after simulated dissolution of 3.4 grams of

Figure 4. Predicted values of pH and Eh during dissolution of West Valley glass (solid lines) and DWPf glass (dashed lines) in J-13 water at 90°C.

glass. The Eh drop is caused by the depletion of dissolved oxygen in solution. Np and Pu concentrations, which are constrained by equilibrium with NpO_2 and $\text{PuO}_2(\text{c})$ during the Eh drop, decrease abruptly from $10^{-6.1}$ to $10^{-8.6}$ M and $10^{-10.2}$ to $10^{-14.8}$ M, respectively. Ru concentration increases until the Eh drop, which causes Ru concentration to drop by 5 orders of magnitude from $10^{-12.7}$ to 10^{-19} M. Mn concentration reaches a maximum at $10^{-11.5}$ M before the Eh drop, and then decreases steadily. Concentrations of Mn, Np, Pu and Ru vary because their speciation and equilibrium reactions between the major aqueous species of these elements and their precipitates are dependent on the oxidation potential of the solution.

Behavior of elements such as Ca in solution is erratic because of competition by a variety of precipitates. For example, the concentration of Ca is maintained at a constant level of $10^{-3.5}$ M (12 mg/kg) while dioctahedral smectite, calcite solid solution and fluorapatite co-precipitate. Ca begins to become depleted in solution, however, after dissolution of approximately $10^{-1.5}$ (0.035) grams of glass, and when halite and tremolite precipitate after $10^{-1.4}$ (0.24) grams of glass dissolution. Equilibration with respect to hydroxyapatite near the end of the simulation causes Ca molality to increase slightly, although Ca concentration is still restricted to a few $\mu\text{g/kg}$. Analytical concentrations of Ca and other elements can be expected to vary significantly during a laboratory experiment.

Dissolution of 0.33, 1 and 10 grams (0.12, 0.37 and 3.7 cm^3) of West Valley glass into 1 kg of J-13 water during the simulation results in the precipitation of 0.2, 0.6 and 5.4 g (0.064, 0.161 and 1.72 cm^3) of secondary phases. If the surface area of the top of the glass canister is assumed to equal 0.275 m^2 [11], and if it is assumed that the secondary precipitates are distributed evenly over the top surface, every cm^2 of the glass surface would contain 7×10^{-6} , 2×10^{-5} and 2×10^{-4} cm^3 of secondary precipitates. Alternately, uniform layers with thicknesses of 0.07, 0.2 and 2 μm , respectively, would coat the glass surface. Radionuclide-bearing precipitates, which are dominated by petalite and B_2O_3 , comprise only about 33 volume % of the total precipitates, however. Given the potentially small quantity of precipitates formed during reaction, and the fact that a radionuclide-bearing phase of interest may comprise a small fraction of the total volume of precipitates, it may be difficult to detect some radionuclide-bearing phases formed during laboratory experiments.

Solid Precipitates

The sequence and relative masses of predicted solid precipitates accompanying dissolution of DWPF SRL-165 frit glass are shown in Figure 5 as a function of the logarithm of the mass of dissolved glass per kilogram of J-13 water. Raising the temperature of J-13 water to 90°C prior to glass dissolution results in the precipitation of talc, dioctahedral and trioctahedral smectite, and a calcite solid solution. The compositions of the solid solutions are equivalent throughout the simulation to those described in the West Valley simulation.

The general sequence and compositional trends in precipitates are the same in the DWPF and West Valley simulations, although variations exist because of differences in glass chemistry. The DWPF glass under consideration contains a greater proportion of U than West Valley glass, but it does not contain P. The $\text{UO}_2(\text{H}_2\text{PO}_4)_2$ aqueous species, which complexed the majority of the U in solution during the West Valley simulation, could not form to sequester U in the DWPF simulation. U concentrations are, therefore, limited to less than 0.1 mg/kg in the DWPF simulation, but increase to 49 mg/kg in the West Valley simulation, despite the fact that the U content of the DWPF glass is greater than the West Valley glass. Haiweeite and $\text{Na}_2\text{U}_2\text{O}_7(\text{c})$ precipitate on DWPF glass to sequester released U that can not be held in solution.

Higher values of pH at equivalent number of grams of glass dissolution in the DWPF simulation cause $\text{Am}(\text{OH})_3(\text{c})$ to precipitate rather than $\text{Am}(\text{OH})\text{CO}_3(\text{c})$. Nb_2O_5 crystallizes after greater amounts of glass dissolution in the DWPF simulation than the West Valley simulation because DWPF glass contains less Nb than West Valley glass. Bixbyite (Mn_2O_3) precipitates in the DWPF simulation when Eh drops from 0.46 to 0.25 v after dissolution of 5.9 grams of glass, as in the West Valley simulation.

Approximately 0.003 grams of DWPF and West Valley glass dissolve per kilogram of J-13 water before glass dissolution has a significant effect on solution composition and solid precipitates, except for equilibria involving elements such as Co, Mn, Ru, Th, P, Pu and Ni. Solid precipitates containing these elements are extremely insoluble, and any degree of glass dissolution will tend to cause supersaturations in J-13 water.

Figure 5. Predicted paragenetic sequence of secondary solid phases formed during dissolution of DWPF glass in J-13 water at 90°C (see text).

Solution Chemistry

Solution chemistry resulting from dissolution of DWPF glass in J-13 water is shown in Figures 6 and 7 for selected elements as a function of the logarithm of elemental molality and the logarithm of the number of grams of dissolved glass per kilogram of J-13 water. Values of pH and Eh during dissolution are shown in Figure 4. The general compositional trends and limitations on solution composition observed in the West Valley simulations are present in the DWPF simulation.

The behaviors of Np and U in solution during the simulation reflect the influence of both the changing chemical characteristics of the fluid phase and constraints imposed by solid equilibria. Np concentration peaks at $10^{-6.4}$ M (0.1 mg/kg), but then falls to 10^{-9} M (2.5×10^{-4} mg/kg) when NpO_2 equilibrates. Note that the maximum Np concentration exceeds the concentration finally imposed by NpO_2 . The concentration of U, in contrast to Np, varies even when halweeite is precipitating. U concentration reaches $10^{-7.3}$ M (0.011 mg/kg) prior to halweeite saturation. Halweeite precipitation causes a temporary drop in U concentration to a minimum of $10^{-7.8}$ M (0.004 mg/kg). U concentration then increases again, only to decrease steadily after 1 gram of glass dissolution.

COMPARISON BETWEEN SIMULATION AND EXPERIMENTAL RESULTS

Extent of glass dissolution, expressed in this paper as the mass of dissolved glass per kilogram of water, can be compared to the extent of reaction represented by laboratory investigations if 5 is assumed to be released congruently from glass and is not sequestered by any phase. Dissolution of SRL 165-type glasses by Bates et al. [10] at 90°C , for example, resulted in less than 0.2 grams of glass dissolution per kilogram of J-13 water over 230 days. Up to 0.4 grams of ATM-1c and ATM-8 glasses dissolved per kilogram of water within 56 days in similar experiments by Bates (1987, pers. comm.). In comparison, the simulations described in this report involve dissolution of 10 grams of glass per kilogram of water, which represents much greater amounts of dissolution than were achieved in the laboratory studies. The upper limit on estimates of the mass of glass dissolved during Bates et al.'s experiments is shown in Figures 1 and 5 for reference. Even though the experimental conditions during Bates et al.'s experiments were not identical to the conditions of the simulation, the above comparison emphasizes the importance of establishing a common frame of reference before using experimental data to judge simulation predictions.

Precipitates predicted to occur during glass dissolution agree in a general sense with the types of precipitates observed during various laboratory investigations with SRL, PNL 76-68 and DWRG glasses, whose compositions overlap those of the West Valley and DWPF glasses considered herein. A number of precipitates that have been observed during various experimental studies are compared with corresponding phases that precipitated during the simulations in Table 3. No reference to the timing or sequence of occurrence of precipitates is implied in Table 3, nor are the experimental conditions necessarily identical to those in the simulations. Results from vapor phase alteration experiments [9] designed to accelerate reaction kinetics and mimic the effect of time are included in Table 3. Significant deviations between experimental and simulation results involve the precipitation of zeolites and Ca-silicates. The majority of zeolites and Ca-silicates listed as experimentally observed precipitates in Table 3 were not provided for in version 324:R48 of the EQ3/6 thermodynamic data base used in the calculations. Recent additions to the data base of a variety of Ca-silicates should enhance the ability of EQ3/6 to generate realistic precipitates. In the

Figure 6. Predicted concentrations of B, Ca, Li, Ni, Si, Sr and Tc in solution, expressed as the logarithm of molality, resulting from dissolution of DHPF glass in J-13 water at 90°C.

Figure 7. Predicted concentrations of Am, Mn, Np, Pu, Sn, Th and U in solution, expressed as the logarithm of molality, resulting from dissolution of DHPF glass in J-13 water at 90°C.

meantime, however, mesolite is the only zeolite predicted to precipitate during the simulations, and Ca-rich smectites precipitate instead of zeolites.

Unidentified and amorphous precipitates containing Si, Fe, Ni, Al, Sr, U and other elements are frequently produced in laboratory investigations (Table 3; [8]). These precipitates may be represented in the simulations by the wide variety of oxides and hydroxides that precipitate from solution. Extremely small quantities of precipitates are predicted to form for many radionuclides because of their small concentrations in the glass. Detection of precipitates formed during laboratory investigations, may, therefore, be difficult. Validation of prediction results must occur not only with analysis of precipitates, but also from variations in fluid chemistry which are sensitive indicators of precipitate formation.

Table 3. Comparison of experimentally observed precipitates with precipitates predicted by simulating reaction of West Valley and DMPF glasses with J-13 water at 90°C (see text).

<u>Experimentally Observed Precipitates</u>	<u>Predicted Precipitates</u>
smectites [8,9,12,13,14,15]	dioctahedral smectites (nontronite)
Mg-silicates [8,9,12,13,14,15]	trioctahedral smectites (saponite)
	talc
Fe-bearing phases	dioctahedral smectite (nontronite)
Fe-silicates [8,10,15]	hematite
ferrihydrite [12]	andradite
maghemite [14]	
magnetite [14]	
Fe-oxide or hydroxide [17]	
Ni-bearing phases	Ni ₂ SiO ₄
Ni-silicates [8,16]	
Ni-Fe silicates [14,16]	
eucryptite [18]	petalite
zeolites	mesolite
garronite [9]	
analclime/pollucite [8,9,17,18,19]	
thomsonite [9]	
Na-zeolite [18]	
Ca-bearing silicates	mesolite
gyrolite [9]	Ca-rich dioctahedral and
tobermorite [8,9]	trioctahedral smectites
truscottite/reyerite [9]	
Ca-silicates [8,14,16,18]	
U-bearing minerals	haiweeite
wecksite [8,9]	
Ca-U silicate [17]	
Ba-bearing phase [10,16]	witherite
Zn-Si phase - willemite? [12,17,20]	zincite
borosilicates [14,19]	B ₂ O ₃
aragonite [9]	calcite
arsenate apatite [17]	fluor- and hydroxy-apatite

A general correspondence of the elements sequestered by solid phases appears to exist between laboratory results and theoretical predictions, although the exact nature of the precipitate may not be predicted. Refinement of the thermodynamic data base, carried out concurrently with critical evaluation of experimental results, will improve the predictive capability of the geochemical models. In addition, phenomena such as materials interactions, radiolysis, sorption, colloid formation, and dissolution and precipitation kinetics must be provided for to ensure relevance to repository conditions.

CONCLUSIONS

Geochemical simulations of reactions between glass waste forms and J-13 water can aid in predicting long-term repository performance at the candidate Yucca Mountain, Nevada site. Initial simulations predict that radionuclides and other glass components precipitate as oxides and hydroxides, together with carbonates, silicates and phosphates. Precipitation of solid phases can be extremely effective in limiting the concentrations of elements

released from glass. Masses of radionuclide-bearing precipitates are, however, sufficiently small that experimental detection of predicted phases may be difficult.

The general compositional trends in precipitates and solution chemistry are the same in the West Valley and DWPF simulations, except for variations arising from differences in glass chemistry. Concentrations of U in solution are controlled by the presence or absence of P in the glass waste form, which appears to be an effective complexing agent for U. The identities of predicted precipitates agree favorably with the types of secondary phases observed in experimental investigations of glass dissolution. Additional work is required to expand and refine the thermodynamic data base, and to provide for additional repository processes, such as materials interactions and radiolysis, in the geochemical model.

REFERENCES

1. T.J. Wolery, Lawrence Livermore National Laboratory, UCRL-52658, 1979.
2. L.R. Eisenstatt, West Valley Demonstration Proj. WVDP-056, rev. 3, 1986.
3. R.G. Baxter, Savannah River Plant Report DP-1606, rev. 1, 1983.
4. J.M. Delany, Lawrence Livermore National Laboratory, UCRL-53631, 1985.
5. B. Grambow, Ph.D. thesis, Freie Universitaet Berlin, 1984.
6. S. Arnorsson, Am. Jour. Sci. 275, 763 (1975).
7. G.W. Brindley and G. Brown, eds., Crystal Structures of Clay Minerals and their X-ray Identification (Min. Soc. Mon. No. 5, London, England, 1980).
8. A.B. Harker and J.F. Flintoff, Nuclear Tech. 76, 263 (1987).
9. J.K. Bates, M.G. Seitz and M.J. Steindler, Nuclear and Chemical Waste Management, 5, 63 (1984).
10. J.K. Bates, T.J. Gerding, T.A. Abrajano, W.L. Ebert and J.J. Mazer, Argonne Natl. Lab., Draft of semi-annual report, July-Dec. 1986, 1987.
11. R.D. Aines, Lawrence Livermore National Laboratory, UCRL-93735, 1986.
12. D.M. Strachan, K.M. Krupka and B. Grambow, Nuclear and Chemical Waste Management, 5, 87 (1984).
13. G.L. Pine and C.M. Jantzen, E.I. duPont de Nemours and Co., Savannah River Laboratory, DR-1742, 1987.
14. J.E. Mendel, compiler, Pacific Northwest Laboratory, PNL-5157, 1984.
15. J.F. Flintoff and A.B. Harker, in Scientific Basis for Nuclear Waste Management VIII, edited by C.M. Jantzen, J.A. Stone and R.C. Ewing (Mater. Res. Soc. Proc. 44, Pittsburgh, PA, 1985) pp. 147-154.
16. J.K. Bates, T.L. Gerding, T.A. Abrajano, W.L. Ebert and J.J. Mazer, Argonne Natl. Lab., Draft of quarterly progress report, Jan-Mar 1987, 1987.
17. R. Haaker, G. Malow and P. Offermann, in Scientific Basis for Nuclear Waste Management VIII, edited by C.M. Jantzen, J.A. Stone and R.C. Ewing (Mater. Res. Soc. Proc. 44, Pittsburgh, PA, 1985) pp. 121-128.
18. P. Van Iseghem, W. Timmermans and R. DeBatist, in Scientific Basis for Nuclear Waste Management VIII, edited by C.M. Jantzen, J.A. Stone and R.C. Ewing (Mater. Res. Soc. Proc. 44, Pittsburgh, PA, 1985) pp. 55-62.
19. B.E. Sheetz, W.P. Freeborn, D.K. Smith, C. Anderson, M. Zolensky and W.D. White, in Scientific Basis for Nuclear Waste Management VII, edited by C.M. Jantzen, J.A. Stone and R.C. Ewing (Mater. Res. Soc. Proc. 44, Pittsburgh, PA, 1985) pp. 129-134.
20. D. Stahl and N.E. Miller, U.S. Nuclear Reg. Comm. NUREG/CR4379, 3, 1986.

This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under contract No. W-7405-Eng-48.