METALLIZED EXPLOSIVES

R. J. Slape

DEVELOPMENT DIVISION

OCTOBER - DECEMBER 1971

Normal Process Development
Endeavor No. 204

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Mason & Hanger-Silas Mason Co., Inc.
Pantex Plant

P. O. BOX 647
AMARILLO, TEXAS 79105
806-335-1581

operated for the
ATOMIC ENERGY COMMISSION
under

U. S. GOVERNMENT Contract DA-11-173-AMC-487 (A)

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

METALLIZED EXPLOSIVES

R. J. Slape

DEVELOPMENT DIVISION

This project consists of exploring the possible value and the characteristics of very thin coatings of metal on explosive particles, along with the development of processes to obtain such coatings.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

October - December 1971
Endeavor No. 204
Acct. No. 22-2-44-01-204

Section G

METALLIZED EXPLOSIVES

ABSTRACT

In addition to the DTA, X-ray diffraction, and Henkin test results on silvered BTF reported earlier; impact sensitivity via drop hammer and chemical reactivity via gas chromatography were conducted with all results generally indicating no significant compatibility problems. One larger batch, ~ 15 grams of silvered BTF, was made from which pressed-to-shape pellets were fabricated at a desired density of approximately 90% of TMD.

DISCUSSION

The 12A impact sensitivities on BTF and silvered-BTF, $H_{50} = 14.0$ cm and 12.1 cm respectively are not significantly different because of the statistical overlap of the two tests.

Results of the chemical reactivity test on BTF and silvered BTF, summarized in Table I, indicated no significant compatibility problems.

Table I. Chemical Reactivity Test
(0.25 Gram Sample at 120 C for 22 Hours)

Sample	Gas Evolved, μl @ STP					Total
	N_2	CO	NO	CO_2	N_2O	
BTF	256.62	3.84	21.01	32.99	4.37	318.83
Ag/BTF	221.46	1.74	42.50	44.15	3.66	313.51

One larger batch, Batch No. 171-10-14-1B, of 15 grams of silvered BTF was made to provide material for 26 pressed-to-shape pellets at approximately 90% of TMD. Analysis of the silvered BTF via helium air pycnometry yielded a TMD of 2.00 g/cc with a composition by volume percent of 1.2/98.8 Ag/BTF. The pellets were pressed mechanically in a punch and die under vacuum at 25,000 psi with a one-minute dwell time. Average density of the pellets was 1.81 g/cc or 90.5% of TMD.

FUTURE WORK; COMMENTS; CONCLUSIONS

The source of some incompatibility indications in silvered HMX and PETN remains an area for further investigation along with measurement of their detonation velocities and pressures. Efforts will also be considered to investigate possible processes for aluminum coating of explosive powders.