DOE/OR/22014--T/

2.1.2 FAILURE MODELS

LINDA M. BRAUN

Ceramics Division
National Institute of Standards and Technology
Gaithersburg, MD 20899

Technical Report

FAILURE MODES AT ROOM AND ELEVATED TEMPERATURES
April 1995

DOE Office of Industrial Technology

Agreement Period to 3/31/95

Research sponsored by the Industrial Energy Efficiency Division, Office of Industrial Technologies, U.S. Department of Energy, under Interagency Agreement number DE-AI05-92OR22014, and under contract DE-AC05-84OR21400 with Martin Marietta Energy Systems, Inc.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED PH

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

INTRODUCTION

Successful development of reliable ceramic composites will depend on an understanding of matrix cracking and damage mechanisms in these materials. Therefore, the objective of the Failure Models subtask is to investigate failure and damage mechanisms in fiber reinforced ceramic composites. Issues such as how fiber coatings, the fiber/matrix interface, residual stresses, and fiber volume fraction affect frictional stresses, fiber debonding, fiber pull-out and failure modes will be examined. The effect of these microstructural parameters on matrix crack initiation, propagation and damage will also be determined. The resulting observations and measurement data will be used to develop theoretical models for damage mechanisms in fiber reinforced composites.

This report presents results concerning the effect of temperature on the failure modes of continuous fiber ceramic composites performed during the last quarter of FY 1993 and FY 1994. The Raman stress measurements and calculations were performed during the last quarter of FY 1994 and the first quarter of FY 1995.

SUMMARY

An investigation of composite failure modes as a function of temperature and fiber volume fraction was performed on SiC-fiber-reinforced Si_3N_4 -matrix composites fabricated by hot pressing. Transition in composite failure mode between noncatastrophic and catastrophic failure was controlled via the variation of fiber volume fraction and testing temperature. Mechanical tests were performed at temperatures ranging from 25° to 1500°C. Matrix-cracking stress and ultimate strength of the composites were measured from load-displacement curves. Both were found to decrease with increasing temperature, but their sensitivity decreased with increasing fiber volume fraction. The tendency for noncatastrophic failure increased with fiber volume fraction, while the tendency for catastrophic failure increased with temperature. The failure mode was demonstrated experimentally to be determined by the fiber bundle strength, and the matrix cracking stress. These two parameters were found to be controlled by the fiber volume fraction and the temperature. Catastrophic failure at high temperatures was found to be mainly a result of fiber strength loss.

The crack growth behavior of these SiC-fiber-reinforced Si_3N_4 -matrix composites fabricated by hot pressing was also investigated as a function of fiber volume fraction and temperature. Both the stress-intensity factor and an energy approach were used in the characterization of the crack growth behavior. Crack resistance increased with crack extension (R-curve or T-curve) as a result of bridging effects associated with the intact fibers. Large-scale bridging was observed, and was considered in the determination of the R-curves. Temperature and fiber volume fraction affected the crack propagation behavior. At room temperature a single crack was initiated at the notch tip; it then branched and delaminated upon further loading. In contrast, at 1200°C, little crack branching was observed. Increasing fiber volume fraction increased the degree of crack branching. Temperature and fiber volume fraction also affected the R-curve behavior. Raising the temperature to 1200°C did not significantly degrade the room temperature R-curve effect. Increasing the fiber volume fraction from 14% to 29% substantially enhanced the toughening effect and the R-curve behavior.

Preliminary work was started on measurement of stress and stress distributions in fibers and

fiber reinforced composites using Raman spectroscopy. An objective of this program is to increase our understanding of fracture processes in continuous fiber-reinforced ceramic composites. To this end, there is a need for information concerning the stress states in fiber-reinforced composites which are toughened by fiber bridging and pull-out mechanisms. The importance of frictional pull-out forces to those forces caused by geometric constraints is unknown. The effect of the toughening component on the stress distribution ahead of the propagating crack is not known. In addition, an understanding of the influence of microstructural parameters (fiber/matrix interface, fiber volume fraction, residual stresses) on the effectiveness of crack tip shielding is required for the optimization of fiber toughening. A thorough understanding of the mechanisms that control toughening, and therefore control fracture, requires an understanding of the stress states in materials. Through the use of Raman-microprobe techniques, the stresses at, and behind, crack tips can be measured. These techniques are used to measure the stresses associated with fiber bridging in continuous fiber-reinforced ceramic composites.

A micro-Raman system with an in situ biaxial stress system was used to investigate and compare bulk SiC and SiC fibers (SCS-6). The micro-Raman system consists of an Ar⁺ laser (488 nm line), an optical microscope and a 0.5 m triple grating monochromator. The detector is a linear diode array consisting of 1025 elements. Lateral resolution of the measurements is $\approx 6 \mu\text{m}$.

Raman spectra have been obtained on SiC fibers (SCS-6), both free standing and incorporated into a glass matrix. Some of the measurements were made on free standing fibers subjected to an applied uniaxial stress. Finally, Raman spectra were obtained for bulk samples of SiC (Hexalloy) for comparison with the spectra obtained from the fibers. The fibers are β -SiC (cubic) and, therefore, we expect that any Raman spectra would be weak. In fact, integration times of ≈ 20 -25 minutes/spectrum were required. The resultant spectra, however, were very complicated as shown in Figure 1, consisting of many overlapping lines. Figure 2 shows the spectra obtained from the bulk SiC (Hexalloy) specimen. Hexalloy is predominantly α -SiC (hexagonal), in contrast to the SCS-6 fibers and its Raman spectrum is essentially featureless except for two fairly sharp and well separated peaks. There appears to be one common peak for the two materials at $\approx 800\text{cm}^{-1}$ which, in the SCS-6 fiber, is strongly dependent on the polarization of the incident light. We have not yet determined the polarization dependence for the Hexalloy, nor have we yet identified the source of the Raman line.

Figure 3 is a schematic representation of an experiment designed to investigate the effect of an external uniaxial applied stress on free standing fibers. The fiber is compressed between two steel plates in series with a load cell. The results of this experiment are plotted in Figure 4, where the maximum peak height of the free standing SCS-6 fiber is plotted as a function of the applied uniaxial compressive stress. The peak height drops precipitously as the stress is increased. The data are very preliminary, but do suggest that, even with such a complicated Raman spectrum, changes in stress might be measurable.

FAILURE MODELS 2.1.2

PUBLICATIONS

1. H.H. Xu, L.M. Braun, C.P. Ostertag, R.F. Krause, Jr., and I.K. Lloyd, "Failure Modes of SiC-Fiber/ Si_3N_4 -Matrix Composites at Elevated Temperatures," *J. Am. Ceram. Soc.*, **78** [2] 388-94 (1995).
2. H.H. Xu, C.P. Ostertag, E.R. Fuller, Jr., L.M. Braun and I.K. Lloyd, "Fracture Resistance of SiC-Fiber-Reinforced Si_3N_4 Composites at Ambient and Elevated Temperatures," *J. Am. Ceram. Soc.*, **78** [3] 698-704 (1995).

SCS-6 Fiber

Δ

Figure 1

Bulk SiC
Hexagonal

Figure 2

Figure 3

SCS-6 Fiber

Figure 4

FAILURE MODELS 2.1.2

PUBLICATIONS

1. H.H. Xu, L.M. Braun, C.P. Ostertag, R.F. Krause, Jr., and I.K. Lloyd, "Failure Modes of SiC-Fiber/ Si_3N_4 -Matrix Composites at Elevated Temperatures," *J. Am. Ceram. Soc.*, **78** [2] 388-94 (1995).
2. H.H. Xu, C.P. Ostertag, E.R. Fuller, Jr., L.M. Braun and I.K. Lloyd, "Fracture Resistance of SiC-Fiber-Reinforced Si_3N_4 Composites at Ambient and Elevated Temperatures," *J. Am. Ceram. Soc.*, **78** [3] 698-704 (1995).