Office of Sponsored Research

August 7, 1997

Ms. Susan Hamrick
Contract Specialist
Department of Energy
Oakland Operations Office
1301 Clay Street
Oakland, CA 94612-5208

RECEIVED

JUL 27 1998

OSTI

RE: Delinquent Final Report for Grant No. DE-FG03-95ER40904
TEES Project No. 46410 SC

Dear Ms. Hamrick:

On behalf of Dr. Peter M. McIntyre, of the Science and Technology Division, the Texas Engineering Experiment Station is submitting the enclosed Final Technical Report for the above referenced grant.

Should you have any questions regarding this report, please contact Dr. McIntyre at (409) 845-772.

Sincerely,

A handwritten signature in cursive script, appearing to read "Shannon Jordan", is written over a horizontal line.

Shannon Jordan
Administrative Assistant

Enclosure

cc: Dr. Peter McIntyre

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

**Portions of this document may be illegible
electronic image products. Images are
produced from the best available original
document.**

JUL 27 1998

Abstract

OSTI

This proposal requests funding for a 3-year renewal of the DOE advanced accelerator R&D (AARD) program at Texas A&M University. Our program to date has focused on the development of the gigatron, a compact high-efficiency microwave driver for future linac colliders. We report results and progress in that project, and plan to bring it to a milestone and conclusion by mid-1995. We propose to initiate a second project, the development of a new technology for ultra-high field superconducting magnets for future hadron colliders. This project builds upon two magnet designs which we have introduced during the past year, which have the potential for a dramatic extension of the achievable field strength for both dipoles and quadrupoles.

During the past year, we have achieved direct emission into vacuum from two gated field-emission cathode technologies, a knife-edge array and a porous silicon structure. Each cathode structure is designed to optimize direct microwave modulation. The gate geometry and drive conductor patterns for this purpose require multi-mask IC fabrication strategies, and have required substantial process development. Cathodes suitable for triode emissive studies have been fabricated successfully. While these proof-of-principle tests are encouraging, considerable effort remains before either cathode could be incorporated within a microwave power device. At the same time, more conventional approaches to high power and high efficiency at C band have been improved to provide r.f. drive performance close to that required for the Next Linear Collider (NLC).

We propose to continue the present effort through the first six months of the extended program. The specific objective is to build and test a round-beam microwave-modulated cathode, which could either serve as the precursor to further development of microwave power devices or as a stand-alone modulated cathode for linacs. We intend to continue gigatron development toward those objectives, and will seek funding from other sources.

We propose to make a major shift in the direction of our AARD program: the development of ultra-high field superconducting magnets for future hadron colliders. During the past year we have invented field designs which promise to extend dipole field strength to 16 Tesla and quadrupole gradient to 300 T/m. We have devised coil fabrication techniques for Nb₃Sn coils which should provide simpler and more reliable fabrication and superior mechanical and thermal performance. One of the magnet designs, the pipe dipole, has a field geometry suitable for use with tape conductor, without the usual limitations due to charging currents, which ultimately could provide a basis for developing practical magnets with A15 or BSCCO conductors. We have formed a collaboration with the Superconducting Magnet Group at LBL, to develop and test magnets embodying these developments. The primary focus of the TAMU program will be dipoles; after the testing of the D20 dipole the primary focus of the LBL program will be quadrupoles. If successful, we would provide a twofold improvement in the state of the art of superconducting magnet technology for future hadron colliders.

A substantial base of equipment is requested from both DOE and the Texas National Research Laboratory Commission (TNRLC), from the inventory of assets which are to be transferred in the termination of the SSC. The equipment would be used to establish facilities for fabrication and testing of model magnets at Texas A&M University. In addition, interim salary support is requested from TNRLC and SSCL to bridge 9 SSC personnel during the transition period from their currently scheduled lay-off through the first months of the proposed grant renewal.

In support of the expanded scope of the program, TEES commits cost-sharing in the form of returned indirect costs, totaling \$800,000 during the 3-year period. A 20,000 sq.ft. facility has been allocated to house the magnet development activity.

The 3-year renewal proposal is structured in two tasks: fabrication and testing of a microwave cathode as a 6-month conclusion of the gigatron project; and high-field superconducting dipole development. For each task a scope of work, a schedule, and a budget are presented. The personnel for the program comprise the present group at Texas A&M University, collaborators at Sam Houston State University, and personnel who would relocate to Texas A&M from SSC and from HARC. The equipment and facilities required for the gigatron conclusion are all in place. The facilities for the dipole development project are available in a 20,000 sq.ft. allocation within a newly acquired building complex at Texas A&M University. A division of effort between the LBL group and the Texas A&M group has been negotiated, which uses to best advantage the expertise and facilities at each institution. The cost of facility improvements and moving and commissioning of the SSC equipment is contained within the cost-sharing accorded to the project by TEES. The objective of the proposed magnet program is to design, build, and test two short model magnets per year throughout the three-year period, thereby providing a meaningful empirical basis for the development a new generation of superconducting collider magnets.

1. Gigatron Program

The first endeavor of our program has been the development of a compact, high-efficiency microwave power source for e^+e^- linac colliders. The luminosity of a linac collider will ultimately be limited by the energy efficiency with which the tremendous amount of microwave power (~ 100 MW/m) can be generated. For this purpose we invented and have been developing the gigatron, a new approach to microwave power tube design^{1,2}.

Gigatron as a microwave power technology.

The gigatron design concept is illustrated in Figure 1-1 and is described in detail in Appendix A. It features three novel developments: First, a gated field-emitter array is employed for the cathode, to produce a microwave-modulated electron beam directly into the vacuum. Second, rather than the conventional round beam, a ribbon beam geometry is adopted to mitigate limitations from space charge. Third, a traveling wave coupler is used to obtain optimum output coupling even with a wide ribbon beam. By contrast, all conventional microwave power tubes begin with a d.c. electron beam, accelerate it, modulate its energy, pass it through a drift region in which it develops a current modulation, then passes it through an output coupler. The modulation/drift section typically sets fundamental limits to the efficiency, power, and bandwidth of power tube technologies. By starting with a modulated beam, gigatron would be able to eliminate these stages altogether. The calculated performance of gigatron would considerably exceed anything yet achieved, and would meet the drive power requirements of linear collider designs²:

- 18 GHz operating frequency;
- 100 MW peak power for a 1 m device;
- 200 kV HV modulation;
- >50% efficiency;
- >40 dB power gain.

Cathode technology development.

Our work to date has focused on the modulated cathode which is the heart of the gigatron concept. We have achieved gated field emission and modulation of emitted beam into vacuum with each of two technologies: a knife-edge emitter array³ with ~ 200 Å edge radius, 1,000 Å gate spacing, and 8 μ m substrate spacing (Figure 1-2); and a porous silicon cathode⁴ with a dense pattern of field-emitting pores and a thin gold gate layer (Figure 1-3). During the past year this work has resulted in the thesis research and completion of degrees by two of our graduate students: Bo Lee (knife-edge arrays) and Don Smith (porous silicon). The copies of both students' theses are attached and provide a detailed report of our research to date.

Program milestones.

We began the gigatron development program in 1988 with a systematic conceptual design of the modulated cathode, ribbon beam geometry, and output coupler. The first great challenge in the development of the gigatron is the demonstration of a viable technology for using gated field emitters under microwave modulation. We extrapolated the possible performance from the then-available field emitter cathodes which had been successfully developed by C.A. Spindt *et al.*^{5,6} for

display applications. While these cathodes achieved high current density (up to 1000 A/cm^2), the drive power required for microwave modulation would severely compromise the power gain and average power which could be achieved in a gigatron. We addressed this problem by developing a design for a resonant input coupler, shown in Figure 1-4. The coupler localizes the current flow which is required to charge and discharge the gate/cathode junction, and thereby improves modulation performance by 20 dB.

In 1990, our tests of tip-array field emission cathodes fabricated by Spindt et al.^{5,6} at SRI enabled us to identify specific features of the cathode structure which limit microwave modulation. These include resistivity of the gate film and substrate, parasitic capacitance between gate and substrate, susceptibility of the gate to damage during high-voltage breakdown, and insufficient dielectric strength on the gate/substrate insulation to support the bias voltage needed to sustain large emission current density. In 1991, we set out to develop two new kinds of highly emissive field emission cathodes: a stripline knife-edge cathode which increases the surface density of emitters by a factor of 100 compared to tip arrays, and a porous silicon cathode, inspired by studies of diodes that had been conducted at the TAMU Dept. of Electrical Engineering⁷.

Our original knife-edge cathode design was improved in 1992 with a new fabrication approach⁸ which produces very sharp, tall blades and a very narrow control gap for modulation, as shown in Figure 1-2. In the summer of 1993, we succeeded in generating field emission into vacuum from the improved knife-edge array, with a turn-on voltage for emission of about 25 V. Our work to date in developing the knife-edge cathodes is presented in the thesis of Bo Lee (Appendix C). While we have succeeded in obtaining gated emission from the new cathodes, we are still struggling with the control of one fabrication process step, which frequently leaves a shard of gold in the crucial control gap, causing shorting of the gate and arc damage to the diode region. This remaining problem should be viewed in a context of complete success in achieving excellent process control over all other process steps, each of which in its turn posed a similarly serious obstacle. We are currently adapting an electroless plating process, developed at IBM, which produces the gate metalization and its gate opening at the knife-edge without the plasma etching step which gives the troublesome shard. This is the last step of the process, and we should then be able to routinely fabricate successful cathodes.

We obtained a very early preliminary success in diode emission from porous silicon layers: 1 mm^2 cathodes delivered 20 A/cm^2 peak current for a gate modulation voltage of only 10 V. After a considerable effort of varying and tuning the manufacturing process parameters, we produced field emission from porous silicon in a triode configuration, directly into vacuum, near the end of 1992 - to our knowledge the first time this has ever been observed. Since then, new record emissivity has been achieved with porous silicon emitters in diode tests (now in vacuum), with a current density of 700 A/cm^2 at 18.6 V modulation in pulsed mode (1.4 A from an area of about 0.2 mm^2). We have developed a triode cathode in which the emission into vacuum is controlled by a thin ($\sim 50 \text{ \AA}$ thick) gold metalization, in a configuration which accommodates low charging impedance and small parasitic capacitance. Our work to date in developing the oxidized porous silicon (OPS) cathodes is presented in Appendix B (Mr. Smith's thesis). We have succeeded in fabricating and testing such cathodes (Figure 1-3). Figure 1-5 shows the first-ever observation of modulated direct emission into vacuum from a gated porous silicon triode.

The fabrication of both cathode devices has required a steadily growing sophistication in process technology. During the past three years, we have commissioned two class 100 clean rooms, a lithography system, a magnetron sputtering system, an oxidation furnace, a mask aligner, two etchers, a wire bonder, a wafer saw, a vacuum test stand, a laser-backscatter end-point detector, and a cryogenic evaporator⁹.

For each cathode technology we have succeeded in controlling the geometry, materials, and surfaces of devices with a feature size of $\sim 1,000$ Å. We have built and tested triode prototypes of each technology. The current density required for the gigatron cathode has been achieved in diode operation, and the cathode gate structure should support a bandwidth up to 30 GHz. Unfortunately however, neither technology is yet capable of producing robust cathodes. Our results to date demonstrate that the goal of 12 GHz emission, 20 A/cm^2 current density is achievable. The required current density has not yet been achieved in triode prototypes, although substantial progress has been made. At the same time, more conventional approaches to high power and high efficiency at C band have improved to provide performance close to that required for the Next Linear Collider (NLC), although the more ambitious TeV collider designs will require gigatron or its equivalent.

Proposed conclusion in 1995.

We propose to continue the present effort through the first six months of the extended program (through July 1995) with the specific objective to build and test a round-beam microwave-modulated cathode, shown in Figure 1-6. The cathode could either form the precursor to further development of microwave power tubes or be used as a stand-alone modulated cathode for linacs. We are seeking funding from other sources to continue cathode development and the gigatron thereafter.

We began the gigatron development in 1988, with an objective to build a prototype power tube in three years. Our progress towards this goal has been paced by the first step: fabrication of the gated field-emission cathode. Fabricating a submicron cathode structure suitable for microwave modulation is a very difficult technology. Many groups have striven towards this goal for other applications and finally abandoned it as unachievable. We have advanced the state-of-the-art in several important respects: we have invented two quite different designs for such a cathode, each of which has far better intrinsic performance for microwave modulation than any previous design; and we have developed fabrication processes by which we have succeeded in building and testing actual cathodes of each design. It has taken six years to achieve what we first projected would take two years. For some comfort in this regard, we note that the first pioneering steps in gated field-emitter cathodes by Spindt took twenty years from concept to practical display devices. It is a difficult technology.

At the same time, we are of course aware that progress has been continuing in the improvement of conventional approaches to the RF drive requirements of linac colliders. Improved designs for both arrays of conventional klystrons and relativistic klystrons have demonstrated the capability to deliver 100 MW power at 12 GHz, the frequency of choice for NLC. We therefore are proposing a terminal extension of this task of our DOE grant, aimed at the limited objective of

demonstrating microwave modulation of a round-beam gigatron cathode. Such a cathode would provide the basis for subsequent development of gigatron and other microwave power devices. It would also provide a directly modulated cathode for linacs.

We are encouraged by our progress, and frustrated by the time consumed in solving the myriad problems in process development and device physics and the remaining challenges facing us. We plan to continue development of the gigatron technology for applications to microwave power, pulse-modulated cathodes, and flat-panel displays. We will seek funding from other sources as appropriate. We cannot justify continued funding under the AARD program beyond the proposed milestone, in light of the improving performance of conventional RF power sources for NLC needs.

Figure 1-1. Isometric view of gigatron concept: gated field-emitter cathode; ribbon beam geometry; traveling wave coupler.

Figure 1-2. SEM image of a knife-edge cathode, showing the knife-edge and substrate, the polyimide dielectric, and the gate metalization flanking the emitting edge.

Figure 1-3. SEM image of a second-generation OPS cathode, showing the emitting surface, the current feed line, and the thin gate metalization over the pores.

Figure 1-4. Detail of gated field-emitter cathode and resonant input coupler.

Figure 1-5. Transfer function for several OPS triodes. This is the first observation of triode operation of an OPS field-emission device.

Figure 1-6. Round-beam gigatron cathode, configured for coaxial 50-ohm modulation.

2. 1994 Progress Report

A. Porous Silicon Cathodes

In mid-1992, we began investigating the possibility that an electron beam could be extracted from a porous silicon layer. This work was motivated by a remarkable discovery⁷ by Y.K. Yue, then a E.E. graduate student at Texas A&M, that such layers exhibit a copious current when configured as a diode, where a surface metalization forms the anode and the substrate silicon forms the cathode. Currents of $\sim 100 \text{ A/cm}^2$ were achieved, and the I/V characteristic exhibited the Fowler-Nordheim dependence characteristic of field emission. The physical origin of the emission process was unclear, and indeed is still a subject of debate and experiment. We set out to study the dependence of the field-emission performance on the fabrication process used to create the porous layer, and to attempt to develop a triode geometry in which the thick anode of a diode would be replaced by a thin gate metalization which could be used to extract the emitted electrons into the vacuum.

Porous Silicon.

Porous silicon was discovered in the 1950's by Uhler and Turner¹⁰ while studying the electropolishing of silicon wafers in dilute hydrofluoric acid (HF) solutions. Within a range of process parameters, the silicon is anodically etched to form a dense array of pores. The pore diameter can be varied over the range $100 \text{ \AA} - 5 \mu\text{m}$, and the pores can be etched to form continuous parallel channels through a layer thickness from $\sim 1 \mu\text{m}$ all the way to the entire thickness of a wafer ($300 \mu\text{m}$). Figure 2-1 shows an electron micrograph of one particular porous layer¹¹ which is produced by seeding the etch process, as discussed below. Figure 2-2 shows an STM micrograph of the surface morphology of a porous layer.

Formation of porous silicon is carried out by anodic oxidation in HF as shown in Figure 2-3. The silicon wafer is connected to the positive terminal of a power supply so that it serves as the anode; a platinum electrode is connected to the negative terminal. The chemical reactions have been studied by several researchers¹². In concentrated HF, the silicon is etched at the surface by the reaction

where h represents a hole, e an electron, and $n < 2$ is determined by conduction band and valence band efficiencies. SiF_2 is an unstable substance; it reacts with HF to form silicic acid (H_2SiF_6) and hydrogen gas.

The role of holes is essential in the anodic reaction. In P-type silicon, where the majority of carriers are holes, the reaction can be carried out easily. In N-type silicon, however, holes must be otherwise introduced in order to carry out the reaction. One way to do this is to illuminate the surface: light with $\lambda < 1.2 \mu\text{m}$ can produce $e-h$ pairs in silicon. High-intensity illumination can be used to produce a large hole density near the surface. Another way to generate holes is to apply sufficient voltage to the electrodes to cause avalanche breakdown in the space charge region.

During the anodic dissolution, a porous layer is formed on the surface of the wafer. A model of this process was developed by Memming and Schwandt¹³ and later by Unagami¹⁴:

- the Si surface is covered with F⁻ ions;
- when an electric field is applied across the Si-electrolyte interface, holes move towards the surface;
- as holes reach the surface, they are trapped on the Si-Si bonds, weakening them;
- Si-F groups form at the surface, and dissolve into the liquid;
- F⁻ ions occupy the holes and release the charge;
- an insoluble surface porous film forms from the deposition of elementary Si during the initial anodization;
- the dopants are leached from the side walls so that the anodic reactions can occur only at the base of the pores.

A wide variety of pore sizes, geometries, and electrical properties can be achieved by varying the critical process parameters: dopant type and density, exposed crystalline plane, current density of anodization, and electrolyte chemistry. As two examples, Figure 2-1 shows an SEM image¹¹ of porous silicon with ~1 μm pore size, 100 μm depth, and extremely regular pore configuration; Figure 2-2 and Figure 2-3 show the surface of a porous layer with pore size ~100 Å, depth ~1 μm , and complex interconnected configuration. The former layer exhibits little field emissivity, while the latter is the most copious field-emission diode ever tested (700 A/cm² at 10 V). The microphysics of the emission process is still the subject of conjecture and experiment.

In the past two years, we have overcome several major milestones in the maturation of this technology. Eight months after beginning our work on oxidized porous silicon field-emitting devices (OPSFEDs), we developed the world's first successful process for fabricating gated field emission triodes from oxidized porous silicon. The results from these devices were extremely encouraging, and warranted further study of the technology. The greatest problem for gigatron performance has been the extremely large gate current which accompanies the emission into vacuum - typically 1,000 times greater than the emission current!

In the past year, we have successfully overcome one hurdle after another to develop a second-generation gated field emission cathode, more suited to the required frequency modulation and power gain. At the time of this writing, the very first of the second-generation devices have been tested. One of these has achieved an emission current equal to the gate current - a dramatic improvement which moves us closer to performance which would be suitable for microwave modulation experiments. Such experiments were the objective of this year's program; we are ~6 months behind our schedule in achieving this milestone with the porous silicon cathode.

In the next year, we plan to execute a careful optimization of the technologies involved in device fabrication. During the balance of 1994, we plan to concentrate our development on the reduction of the gate current which accompanies collector current. The ratio I_g/I_c varies dramatically from sample to sample as we vary the process parameters with which we fabricate the porous layer and its gate metalization. It is critical to understand the origin of the interception and of the dependence on fabrication and geometry if we are to achieve useful microwave modulation.

Figure 2-1. SEM image of a deep porous layer, in which pore etch was initiated by cone seeds and illumination; from Ref. 11.

Figure 2-2. STM image of the surface of an OPS triode, showing the thin gold metalization and the irregular pore apertures: top view.

Figure 2-3. STM image of the surface of an OPS triode: angle view.

Figure 2-4. Diagram of the anodization process for porous silicon fabrication.

1993 Achievement: True Gated Field Emission

Since the development of the OPSFED by W. K. Yue⁷ in 1989, no method for achieving stable three-terminal operation of a porous silicon field emission device had been successful. A vacuum diode configuration fabricated in 1990 by V. Madduri managed to produce up to 19 μA of current across a 2 μm vacuum gap. Nearly 100 V was required to produce this current, however. Using a true gated triode, we were able to produce 40 times the emission current across 1000 times the gap with only one-fifth the applied bias.

A major challenge this year was to achieve gate modulation at the porous silicon surface without obscuring the tiny (~ 100 Å diameter) pore apertures. For this purpose we adapted a cryo-evaporation process developed by Jaklevic¹⁵ at Ford Motor Research. If gold is evaporated onto a substrate at room temperature, up to a layer thickness of ~ 500 Å the gold is highly mobile on the surface and tends to a pattern of isolated clusters rather than a uniform film as the lowest energy configuration. In order to produce a uniform film for thinner layers, it is necessary to reduce the temperature so that the configuration mobility ($\sim e^{-u/kT}$) is reduced. Once a uniform layer has been deposited, the film is stable and will persist after the device is warmed to room temperature. One of the major achievements of the TAMU group for 1993-1994 was the successful commissioning of an ultrahigh vacuum (UHV) cryoevaporator, enabling us to apply ultrathin conductive gold layers onto our OPSFED samples.

First-generation triode tests.

The majority of the 1992-1993 research was conducted with $\langle 100 \rangle$ -oriented p-type substrates with resistivity of .001-.003 $\Omega\text{-cm}$. For comparison, some $\langle 111 \rangle$ substrates with resistivity of .005-.011 $\Omega\text{-cm}$ were also studied. N-type $\langle 100 \rangle$ substrates with a resistivity of .001 $\Omega\text{-cm}$ were also studied at the outset of the research. Inconclusive results were obtained for these samples, and more work on n-type substrates is planned.

Anodization current density was varied in the range 10-130 mA/cm^2 . Most of the samples were anodized for 10 seconds, but a few were anodized for 5 seconds to measure the effect on cathode emission of shorter anodization time. The anodization electrolyte was 3 parts 48% aq. HF to 1 part absolute ethanol. The majority of the samples were oxidized in ambient dry O_2 at 850°C for 45 minutes. Several of the samples were oxidized for 1 hour. Over eighty samples in all were made and tested. They were shadow-coated with 2000 Å of aluminum to form OPSFED's. The transfer function of the devices was measured with a Tektronix Type 575 curve tracer. Scope traces of the transfer functions were taken, and this I-V data was used to evaluate the relative performance of the devices. Fowler-Nordheim behavior was seen in over 65% of the samples fabricated.

Normally a set of 12 devices are tested from each sample wafer. The first four are destructively tested to determine their maximum output current and to get an idea of the operating voltage of the set. For the rest of the devices, the voltage is measured at several emission current levels within the operating limits of the set. It is seen that the operation of the devices is uniform within the set. Operating voltage of the devices ranged from a few volts to in excess of 180 V. Fowler-Nordheim emission current was measured from .1 mA to well in excess of 200 mA.

Transconductance of the devices varied widely, and the exact parameters that control the transconductance are not yet perfectly understood. High transconductance is a priority for microwave modulation. We began experimenting with the HF concentration and the resistivity in 1994. The most ideal diode behavior in an OPS device to date was discovered in early June 1994. Figure 1-5 shows the Fowler-Nordheim plot of the device.

It was hypothesized that the ultrathin gate layer would enable us to apply an electric field to the porous layer, sufficient to produce and modulate field emission, without intercepting the current at the surface, so that the device would function as a cathode to control emission directly into vacuum. This hypothesis was proved to be valid. The utilization of the gate layer resulted in a triode which produced .8 mA of vacuum emission current across a 3 mm vacuum gap. Only 20 V of gate bias was required to produce the emission, as shown in the Fowler-Nordheim plots shown in Figure 2-5. The deviation from a characteristic Fowler-Nordheim is roughly what one expects from the space-charge potential of the gate current in the pores. 200 V of collector voltage was sufficient to saturate the plate characteristic (Figure 2-6).

The geometry used to produce the proof-of-principle OPS triodes was very simple and had a large parasitic capacitance. Therefore the modulation frequency of the devices was limited. Nevertheless, 5 MHz modulation was readily achieved. Oscilloscope traces of these results are presented in Figure 2-7.

Figure 2-5. Fowler-Nordheim plot of the triode emission data of Fig. 1-5.

Figure 2-6. Plate characteristic of the above OPS triodes.

a. 200 kHz.

b. 1 MHz.

c. 5 MHz.

Figure 2-7. Modulated emission of electron current from an porous silicon triode. Top trace is gate voltage; bottom trace is emission current through a 10 k Ω resistor.

Lessons from the First OPS Triodes: Basis for the Stage II Design

The encouraging results from the first-generation OPS triodes were accompanied by some results indicating the necessity of further development of the technology. The construction of the first devices, as mentioned above, had a very simple geometry, in which the porous layer was surrounded by native silicon with a thin oxide layer on its surface. Figure 2-8 is a cross-section schematic of the fabrication process of the proof-of-principle triodes. Figure 2-9 shows the mounting scheme for the devices. In order to make contact with the thin gold gate, it was necessary to apply a patch of conductive epoxy over an area of the actual cathode. This imposed an intrinsic gate interception, and made the effective emitting area somewhat problematic to characterize. As shown in Figure 1-5 and Figure 2-10, there was a 1000 to 1 ratio in gate current to emission current. In addition, the planar region surrounding the gated region presented a large parasitic capacitance (~ 100 pF) which compromised efforts to achieve microwave modulation.

The lack of a well-defined emission area resulted in the loss of a firm number for the actual transmitted emission current density, but the use of the particular gate connection method allowed the measurement of emission current density produced within the OPS matrix. In excess of 700 A/cm^2 was measured on a .5 mm gate connection at 1% duty cycle. We estimate a transmitted emission current density into vacuum of 10 A/cm^2 .

Figure 2-8. Fabrication process for first-generation OPS triodes.

Figure 2-9. Mounting procedure for first-generation OPSFED cathodes. A tubular collector was located ~3 mm from the cathode to complete the test circuit.

Figure 2-10. I-V characteristic of the triode gate current.

Figure 2-11. Fowler-Nordheim plot of the triode gate current.

Process Development for Stage II Cathodes

In order to improve the frequency response of the second-stage OPS cathode, Smith developed the process outlined in Figure 2-12. The so-called "Stage II cathodes" have a parasitic capacitance of less than 20 pF, and allow operation to higher frequency than the first stage devices. In addition, flanking 1 μ m-thick feed lines should provide a well-defined emission area, all-metal construction, and uniform biasing of the ultrathin gate layer (this last point has proved to be somewhat problematic in practice, as discussed below). During the first half of this year, all steps of the Stage II cathode fabrication process have been successfully completed in our clean room facility:

- Anisotropic etching, also called orientation dependent etching (ODE) is used on <100>-oriented substrates to form a series of "mesa" structures. This process has been perfected by the group in the development of the knife-edge cathode structures. Polyimide (PI) spin-on polymer dielectric is then applied, soft baked, and cured.
- A computer-controlled PI curing oven was built and commissioned during early 1994. It enables us to maintain tight control on the PI curing cycle, giving excellent reproducibility, high film density, strong adhesion, and no cracking.
- The cured PI is etched in a Tegal 211 barrel plasma etcher until the silicon mesas are exposed. This step was a key improvement in the Stage II process, and has been perfected. After PI etchback, an MRC Sputtersphere is used to apply an adhesion layer of titanium/tungsten and a 1 μ m gold film to the entire surface. An image-reversal process is then used to remove the gold film and its adhesion layer from the OPS mesas which will be the active area of the cathode. Perfection of this process was a second major process achievement during the past 6 months. Figure 1-3 shows a Stage II cathode after this process step.
- The exposed silicon mesas are then anodized, using the gold feed lines and PI as etch mask. The gold feed lines are formed between the mesas, and the PI greatly reduces the parasitic gate/substrate capacitance in the finished device. The gold and PI form an HF-resistant mask for patterning of the porous silicon (PS).
- The anodization process is used to produce a porous layer $\sim$ 1 μ m thick on the mesas. The anodization of anisotropically etched features provides a higher effective anodization current density than that for anodization of planar surfaces. A low-temperature oxidation cycle is then used to convert the PS to OPS. The PI curing oven is used for this purpose.
- The gate layer is deposited in the final process step, using our cryogenic evaporator system. By evaporating a film of gold onto a substrate at 77 $^{\circ}$ K, Jaklevic showed that a uniform layer can be achieved even with film thickness of $\sim$ 50 $\text{\AA}$.

1. ODE etch, form mesas

2-3. Apply and cure PI

4. Etch PI, expose mesas

5-7. Pattern feed lines

8-9. Form OPS on mesas

10. Apply thin gate layer

Figure 2-12. Process outline for second-generation OPS cathodes.

Preliminary Results from Stage II Emitters

Figure 2-13 shows a cross-section SEM of a completed second-generation OPS cathode. At the time of this writing, the first devices resulting from the Stage II process have been tested. Vacuum triode emission has been obtained. Emission from the first batch of devices was unstable, as with the first generation devices. The devices could not be conditioned to sustain emission at low gate voltage. The triode characteristic exhibited the same 1000:1 ratio of gate to collector current, which would be useless for microwave devices. Figure 2-14 shows a micrograph of a cathode following attempts at conditioning. The regions immediately flanking the feed line have burned along each side: we are producing a fatal level of local Joule heating. We interpret this heating as being due to the large gate current producing a voltage drop on the thin gate metalization, so that only the region immediately adjacent to the feed line receives the full gate voltage. Unless we can find and remove the origin of the large gate current, the OPS cathode will not provide a useful cathode technology.

A second batch of devices produced one sample which exhibited a 1:1 current ratio: the gate current was 1000 times smaller than before, with roughly the same collector current.

The relation of OPS emission to process fabrication

Field emission from porous silicon films has been observed over a wide range of porous silicon formation conditions. An initial parametric search conducted by Smith was targeted at relating device performance to the anodization current. Turn-on voltage of the devices was observed to increase with increasing anodization current density. Shorter anodization times resulted in lower turn-on voltages for the devices. <111>-oriented substrates were seen to give lower turn-on voltages and higher emission currents than comparable <100>-oriented substrates. <111> substrates are not well-suited for anisotropic etching of capacitance-reducing structures, so therefore more consideration was given to <100> substrates.

The results of parametric morphology studies from the literature show that the pore depth is linearly related to the anodization time, and that larger anodization current density results in larger pore diameter¹⁶. The results of these morphology studies combined with the results of Smith's electrical characterization studies give a first-order picture of the emission mechanism.

The electric field in the porous matrix is parallel to the pore walls in the body of the matrix. This field is distorted and enhanced in the neighborhood of the pore tip. The shallower OPS layers start with a stronger electric field, and thus require less voltage to initiate emission. Layers with larger pores have less electric field enhancement in the pore tip region, and thus require larger voltages for emission.

The small pore size associated with degenerately doped silicon (on the order of 10 nm) makes detailed study of the porous morphology exceedingly difficult. The actual formation mechanism of PS in p-type silicon is still poorly understood. The morphology change associated with the oxidation process has not been extensively studied, and greatly impacts the final OPS morphology. The role of pore branching and the effect of crystal orientation on emission are further considerations for a full understanding of this phenomenon.

Optimization of the gate transmission.

Stimulated by this latest result, we are now proceeding to a systematic study of gate interception and its link to the fabrication process. Good transmission requires that the morphology of the OPS layer be matched to the gate layer. The second-generation OPS field-emission cathode should enable us to achieve such a match. It provides a well-defined emission area, from which emission current density can be precisely measured. Good separation of the feed line areas ensures that all gate current in the device is due to a mismatch of pore size and film thickness or to intrinsic features of the electron transport in the pores. For transmission, the most crucial steps in the process are those in which the flanking gold feed lines are formed and the thin gold is deposited over both the porous layer and the feed lines. Our work to date suggests that the contact between feed line and thin gold is intermittent, and may be the cause of both the poor gate transmission and the local heating. We are currently trying several modifications to the process aimed at extending the thick gold feed line slightly onto the porous region to provide a more robust junction between the two metalizations.

One such modification would utilize the etch seed process of Lehmann¹¹. A pattern of dots is defined lithographically on the wafer surface, on a pitch of $\sim \mu\text{m}$. The dots are used as a resist mask for an initial ODE etch process, which produces conical depressions in the wafer surface. The electric field in the Si concentrates at these sites, so that the etch process proceeds preferentially there and produces a pattern of extremely straight pores. This process has been used by Lehmann to produce highly regular arrays of large-size ($\sim 1 \mu\text{m}$) pores (Figure 2-1). We plan to measure emission from smaller-size pores made using the same procedure for regularization. The removal of brachiation should reduce the gate interception problem.

Figure 2-13. SEM cross-section of a completed second-generation knife-edge cathode.

Figure 2-14. SEM image of the OPS region surrounding the feed line on a second-generation cathode after testing.

B. Knife-Edge Cathodes

For the past 35 years, a number of investigators^{6,17} have developed several approaches to the fabrication of sub-micron field-emitting tips and associated gate structures as the basis for vacuum microelectronics. The motivation is simply stated: if the size of an emitting cathode could be reduced to submicron scale, and if a gate electrode could be configured above the cathode with a comparable spacing, then a few volts of modulation would suffice to control field emission. Since the transit time from cathode to anode also scales with the gate spacing, such devices should exhibit large bandwidth. Appendix C (Dr. Lee's Ph.D. thesis) presents a detailed history of the development of these devices and the process technology employed.

The most successful approach to field-emitter cathode fabrication has been that of C.A. Spindt⁶, who uses a sequence of etch and directional evaporation steps to grow a conical tip inside a $\sim\mu\text{m}$ aperture in a gate metalization. Figure 2-15 shows an SEM micrograph of his tip arrays. The tips exhibit uniform size and geometry, and large arrays have been operated with long lifetime at currents of up to 1000 A/cm^2 .

Importance of gate/base geometry for microwave modulation.

For tip arrays made using Spindt's technique, the gate aperture and the spacing of the gate to the tip have a natural scale which is tied to the thickness of the dielectric layer beneath the gate: for a dielectric layer of $1.5 \mu\text{m}$, necessary for adequate dielectric strength, the gate opening is comparable. This limits the field concentration which can be created at the tip, while producing a large parasitic capacitance between the gate layer and the substrate. These features of tip arrays are of little consequence for the display applications for which they were first developed, but present a major limitation for microwave power applications.

Figure 2-16 shows the key features of the tip geometry and of our knife-edge geometry which govern microwave modulation (see Appendix A). The figure of merit for high-frequency modulation is the ratio of the emitted current to the drive current required to produce the necessary voltage modulation:

$$\frac{P_{\text{out}}}{P_{\text{in}}} = \frac{I_c V_c}{I_s^2 Z_s} = \frac{A E^2 e^{-B\phi^{3/2}/E} V_c}{(\omega C_s V_s)^2 Z_s}$$

The electric field at the tip and the gate capacitance are

$$E_s \approx V_s / r, \quad C = \epsilon p^2 / s$$

where $r \sim 0.5 \mu\text{m}$ is the radius of the tip, s is the gate/substrate spacing, and p is the distance between tips in the array. Since $r \sim s/3$ and $p \sim 5r$ are practical limits for the Spindt fabrication approach, the "gain" depends upon tip radius as

$$\frac{P_{\text{out}}}{P_{\text{in}}} \propto s^2 / r^2 p^2 \sim 1 / r^2$$

Figure 2-15. An array of gated field-emitting tips, fabricated by C.A. Spindt (Ref. 6).

The fabrication of such a device preser is a major challenge. Were we to try to use lithography and etching directly to create the gate/base geometry, it would require submicron lithography at the limit of what is achievable in the best chip-industry equipment. Dr. Lee devised a clever alternative, described below, which achieves this geometry in a controlled, reproducible process, using the relatively old fabrication equipment which we have been able to assemble in our laboratory.

The enhancement in microwave gain should be a factor of $\sim 10^3$. A more detailed presentation of this analysis is contained in Appendix C; this summary demonstrates our motivation in developing the knife-edge cathode with small gate/edge control gap and large gate/base spacing.

$$\frac{P_{om}}{P_m} \propto s^2 / g r$$

We have devised a means to fabricate knife-edge arrays in which the knife-edge is flanked by a gate metallization with a control gap $g \sim 0.2 \mu\text{m}$, a knife-edge radius $r \sim 200 \text{ \AA}$, and a gate/base spacing $s \sim 8 \mu\text{m}$. The analogous dependence of "gain" on these parameters is roughly

Figure 2-16. The key features of device geometry for a Spindt tip array and a knife-edge array.

Knife-edge cathode fabrication process.

Figure shows our fabrication process for producing an optimum emitter structure. Each of the thin film process techniques is described in detail in Appendix C, chapters V and VI.

- 1) Pattern the SiO_2 mask on a (110) silicon wafer using standard photolithography technique. The mask pattern has groups of parallel lines with identical line width. The lines are accurately aligned with one of the two (111) planes that are perpendicular to the wafer surface.
- 2) Use an ODE process¹⁸ to etch out a perpendicular wall structure ($\sim 8 \mu\text{m}$ high) on the wafer. Each wall corresponds to a SiO_2 mask line. The wall typically has an aspect ratio $\sim 600:1$ if the resist lines are accurately aligned along the (111) crystalline direction. (Figure 2-18)
- 3) Apply a Dash-type etch¹⁹ to convert the walls to knife-edges. A $\sim 6^\circ$ slope can be formed, sharpening the rectangular prism to a knife-edge at the top. (Figure 2-19)
- 4) Further sharpen the edges by a low temperature oxidation process²⁰. The thickness of the oxide is in a range of $0.1\text{-}0.2 \mu\text{m}$. (Figure 2-20)
- 5) Apply a layer of polyimide (PI) coating²¹. The thickness of the PI layer ($\sim 10 \mu\text{m}$) should be greater than the height of the knife-edges so that the surface is planarized. (Figure 2-21)
- 6) Etch back the PI layer to expose the wedges. A plasma etch is needed for this process. We had to develop a laser diagnostic method (Figure 2-22), in order to accurately signal the moment when the knife-edge is first exposed above the PI surface; we can then precisely control the final height of the silicon knife-edge above the gate metalization.

- 7) Deposit the gate metal layer (Au). We have used magnetron sputtering and a Ti:W adhesion layer to produce a uniform .5 μm gold metalization with excellent adhesion to the PI surface. (Figure 2-23)
- 8) Apply spin-on photoresist, and etch back to expose the raised mounds in the metalization over the knife-edges. (Figure 2-24)
- 9) Wet-etch the exposed metalization so that the top of the SiO_2 wedge is exposed.
- 10) A buffered HF solution is used to remove the SiO_2 from the top and sides of the knife-edge, exposing the finished Si knife-edge. The gap separating the knife-edge from the gate metalization has been controlled by the thickness of the thermally diffused SiO_2 layer, which can be controlled with extreme precision to any desired value in the range 0.05-2 μm . (Figure 2-25)

The process outlined above has the following features:

- The process is self aligned. Only one lithography step is needed to produce the emitter and the gate. The finished structure has the emitter edge sitting right at the center of the gate gap.
- The oxidation process (step 4) serves dual purposes: It sharpens the emitter edge, and it defines the gate-to-emitter spacing. Silicon thermal oxidation can be very uniform and well controlled. This makes it possible to obtain a gate-to-emitter spacing anywhere around 0.1 μm .
- The size of the gate opening is independent to the emitter height. The process builds the emitter body before it makes the gate layer, and the gate metalization is separated from the silicon edge only by the thickness of the SiO_2 layer no matter how high the emitter is.
- The positions of the gate layers with respect to the emitter edges are adjustable. This is done by varying the emitter angle θ , the oxidation thickness, and the depth of PI etchback. In fact, geometric parameters like h, g, θ , s, and t are all adjustable in the process.

Figure 2-17. Fabrication process for knife-edge cathode arrays.

Figure 2-18. Rectangular prisms etched on 110 silicon using ODE.

Figure 2-19. Wedges formed by Dash etching the rectangular prisms.

Figure 2-20. Thermally diffused SiO₂ layer in wedges.

Figure 2-21. Planarized layer of polyimide covering the wedges.

Figure 2-22. Laser back-scattering diagnostic for end-point detection to etch PI layer until wedges are exposed.

Figure 2-23. Gold metalization on PI surface.

Figure 2-24. Etched metalization exposing SiO_2 wedges.

Figure 2-25. Final geometry, where SiO_2 has been etched back to expose knife-edge and gate.

Cathode tests.

We patterned 2" lithography masks to fabricate 16.1 mm² cathode arrays, distributed over the wafer surface. Each array contains two 15-line groups of 400 μ m-long knife-edges and wire-bond pads for connection to gate and substrate. After fabrication, we diced the cathodes and mounted test specimens on a TO-5 header just as we did for the OPS cathodes. We then installed them in our test chamber and performed conditioning and emission experiments.

Figure 2-26 shows the emission characteristic measured on two cathodes from the same batch. Figure 2-27 shows a Fowler-Nordheim plot of the same data. In his thesis (Appendix C) Lee calculates the emission current from a line density of 100 emitting sites/ μ m on a knife-edge of our geometry, assuming a work-function of 4.35 eV typical of silicon. The curves in Figure 2-26 show excellent agreement with the measured emission from each cathode. That is the good news.

The bad news is that the cathodes would typically develop shorts after a relatively brief period of operation (frequently only minutes), and arc over gate $\rightarrow$ knife-edge, destroying portions of the gold surface in the process. Figure 2-28 shows a cathode surface after such an arc. We found that the arcs were caused by a sub-microscopic ribbon of gold which commonly remained loosely attached at the bottom of a V-trench between the PI and the Si knife-edge. Figure 2-29 shows one such ribbon. The ribbons form because the PI etch forms a shallow V-groove at the PI-SiO₂ interface. The ribbons are only loosely attached, and wave around much like an electrometer when voltage is applied to the cathode.

After much painstaking investigation, it appears that the V-grooves are an unavoidable result of the plasma etch of the PI. Unless we can find an alternative process step which will eliminate the gold ribbons, it is unlikely we can make useful cathodes.

Process improvements to eliminate arc-over.

Happily, we have identified such a process and tried it successfully on a first batch of cathodes. Viehbeck (IBM) has perfected a technique²² in which he implants a PI surface to produce electrochemical bond precursors for metal bonds, and then performs electroless plating of Cu directly on the PI surface. The Cu surface is uniform, has small grain size, and is suitable for subsequently depositing either Au or Cr, either by sputtering or electroplating. Best of all, the Cu does not plate onto SiO₂, so that only the gate metalization is formed: no metal is deposited on the region where we currently have to etch it away.

Dr. Viehbeck's group has prepared a batch of our cathodes, in which they performed the above steps after we had completed the initial geometry of the knife-edge and PI. Figure 2-30 shows the result. The metalization is uniform and dense; there is no metal on the knife-edge; there is no V-groove in the PI, and no ribbon of metal adjacent to the knife-edge. The surface exhibits some micro-debris, which is an artifact of the IBM process environment and can be eliminated by conducting the fabrication in a clean-room environment.

We are currently setting up to test cathodes made using this technique. We have high hopes that it will prove to solve the shorting problem, so that we can begin to characterize the cathode performance.

Figure 2-26. Triode emission characteristic of knife-edge cathodes.

Figure 2-27. Fowler-Nordheim plot of knife-edge cathode response.

Figure 2-28. SEM image of a cathode surface after testing.

Figure 2-29. SEM image of a gold ribbon, formed in a V-groove at the knife-edge/PI boundary.

Figure 2-30. SEM images of Cu-plated knife-edge cathode.

3. Proposed 1995 Scope of Work

We propose to continue three activities in our cathode development through the first half of 1995: fabrication of knife-edge cathodes using electroless plating to eliminate the gold-shard problem; tuning of the OPS fabrication process to minimize gate interception; and construction of a round-beam cathode assembly as a stand-alone unit for 3 Ghz emission studies.

The IBM group is applying electroless plated metalizations to ten wafers on which we have carried through the cathode fabrication through step 6 above. The wafers have a sequence of relative heights of the knife-edge above the polyimide and of oxide thickness (gate gaps). We will select cathode arrays from each wafer, and prepare them for testing. We will seek to identify the optimum geometry for each of the above variables, and test the emission properties. We have demonstrated that the electroless process eliminates the metal shard which results when we etch a sputtered metalization; we hope to demonstrate stability against the breakdown which the shard produced on the sputtered samples.

We will tune the pore size and the pore geometry (straight vs. brachiated pores) in the Stage II OPS cathodes, and measure the emissivity and gate interception. We have recently completed a mask set which makes it possible for us to seed the pore formation on a regular pattern of sites by lithographically defining and etching a pattern of conical depressions in the Si surface, as discussed above. This process has been used by Lehmann¹¹ to produce such regular arrays of large-size ($\sim 1 \mu\text{m}$) pores (Figure 2-1). We plan to measure emission from smaller-size pores made using the same procedure for regularization. The removal of brachiation should reduce the gate interception problem. We are also studying the one cathode which operated without large gate interception to try to understand what differences in its morphology could explain the improved performance.

With the fruits of one or both of the above efforts, we plan to construct a cathode assembly suitable for mounting in a gun configuration. Figure 1-6 shows a cathode mount which brings the microwave modulation input in through a coaxial stem which is matched to present a 50Ω load. A d.c. bias would be provided using an external d.c. block, so that the rf amplitude would turn emission on and off from an appropriate d.c. offset. The cathode assembly is designed to mount in our vacuum test stand. The rf drive, water-cooled collector, and microwave stem structure are on hand.

The cathode structure will be built in a fashion which makes it appropriate for mounting onto a diode for a test power tube, or as a free-standing modulated cathode for a linac injector. After initial tests at Texas A&M, we would plan to take it to Mission Research, who have developed a time-slice diagnostic capable of measuring beam emittance parameters as a function of time during an rf waveform.

4. High-Field Superconducting Magnets

As we strive to extend the high-field frontier for superconducting dipoles and quadrupoles, we must develop viable alternatives for two of the most fundamental ingredients of superconducting accelerator magnets that have served us so well for the past two decades: the NbTi superconductor and the $\cos \theta$ coil geometry. NbTi has no useful current-carrying capacity beyond ~ 10 Tesla. The only alternative today for pressing to higher field is Nb₃Sn, which extends j_c performance to ~ 18 Tesla. During the past decade the technology for producing high- j_c cable from Nb₃Sn has matured well, thanks to the programs at Brookhaven, Twente²³, Ansaldo, and LBL²⁴. We are only beginning, however, to master the techniques of winding, curing, impregnating, and collaring such coils for collider dipoles. To that end LBL is currently fabricating D-20, a prototype 13 Tesla $\cos \theta$ dipole using two inner shells of Nb₃Sn cable and two outer shells of NbTi cable. Figure 4-1 shows the cross-section of D-20. Figure 4-2 shows a coil subassembly being prepared for reaction bake. D-20 is currently being built and will be completed this winter and tested during Spring 1995.

The design and development of D-20 has already taught us a valuable lesson about the second major challenge: 13 Tesla is likely the limit for dipoles using the $\cos \theta$ coil geometry which has been the basis for all collider magnets used to date. In order to grade the conductor with decreasing field in the coil region, a multi-shell coil is used. The fragile strands of Nb₃Sn cannot accommodate keystoneing to conform to the cylindrical geometry of the $\cos \theta$ design. The coil placement of D-20 has been adapted to achieve the necessary current distribution using rectangular cross-section cable, but a total of four shells are required. While this approach should work for the 13 Tesla design field of D-20, extending the design to higher field would entail yet more shells, creating a coil package which is difficult to build, react, support, and maintain conductor tolerances. Pushing field strength to the limits of Nb₃Sn conductor will require that we develop an alternative coil geometry, which can achieve a greater effective packing fraction of conductor near the beam tube, produce the required field quality for collider operation, and be realistically manufactured. Happily a parallel set of developments at Texas A&M and LBL are converging on two concepts which have this potential.

Two years ago we invented the pipe magnet, a wholly new approach to high-field dipole design²⁵. Figure 4-3 shows a 13 Tesla design for the pipe magnet. The magnetic flux is guided by a coil distribution along the entire magnetic flux circuit, rather than by a coil clustered closely to each beam tube in conventional $\cos \theta$ designs. This approach conveys two important benefits: no stress concentrations (better mechanical support), and no persistent-current multipoles (fields do not fringe through the coil package). The invention of the pipe dipole resulted from our development of new calculation techniques for optimizing the design of structured coils²⁶, in which the coil shape and current elements are optimized to produce the best possible field quality subject to defined constraints on the coil boundaries and steel placement.

Following analysis of the pipe concept and the lessons from building D-20, the LBL and TAMU groups are beginning the joint development of several magnets which incorporate the de-

sign and fabrication innovations at both collaborating institutions. The TAMU program will focus upon primarily on the dipoles; the LBL program will focus primarily on the quadrupoles.

Magnet designs.

Figure 4-4 shows a **16 Tesla block-coil dual dipole**, which utilizes a block coil configuration and Nb₃Sn Rutherford cable. All coil elements are would as simple racetrack coils, with a novel provision for end winding which simplifies fabrication and provides improved end support. The block-coil design has the best magnetic efficiency of any high-field magnet, and provides for simple assembly and uniform coil prestress. The calculated fields exhibit multipoles which are less than one unit (10^{-4} cm⁻²) over a continuous 20:1 range of magnetic field. The calculated persistent-current sextupole hysteresis is 10 times smaller than in any cos θ dipole.

In the **pipe dipole**, the confinement of flux within the coil envelope uniquely makes it possible to use an inner coil element of tape conductor without the usual problems of AC losses and persistent-current multipoles due to penetration of fields through the face of the tape. The ability to use tape conductor would open two long-term possibilities for pushing still further the high-field envelope: Nb₃Sn tape has twice the critical current density j_c of cable conductor, and is amenable to using ternary components to enhance high-field j_c ; BSCCO tapes are now being fabricated in significant lengths with $j_c \sim 250$ A/mm² and critical field above 30 T.

We have also applied the block-coil approach to design a **330 T/m quadrupole** suitable for the low- β insertions at CERN's LHC. The design of the high-field quadrupoles for the intersection regions of LHC is a challenging task. A gradient of 250 T/m is required, with a 7 cm aperture. The block coil quadrupole would provide 30% greater gradient, operating at 4.2 °K.

Fabrication innovations.

The ends of a superconducting magnet have always been the hardest problem for design and fabrication and the most likely site for failure in operation. The coil elements for the above magnets are configured as rectangular coil packages, resulting in a considerable simplification of tooling, winding, assembly, and quality control. The ends of those coil elements which flank the beam tube must be bent out-of-plane to accommodate the beam tube, however. We have devised and demonstrated a procedure by which these coils can be wound as flat coils and then bent out-of-plane at the ends after winding, using a process which is used in industry for large motor coils.

All of these magnets feature realistic prestress strategy, copper stabilization suitable for realistic quench protection, and a design field distribution which maintains collider-quality uniformity over a 20:1 dynamic range.

The insulation system for Nb₃Sn magnets is another challenge for high-energy colliders, because the requirement of epoxy impregnation after winding severely limits heat transport in the coil package. We have devised an alternative insulation system, consisting of a resin-ceramic-glass filler. The filler is impregnated between the strands of the Nb₃Sn cable and E-glass cloth sock over each cable and soft-cured before coil winding. This system serves four important functions to provide stability to the fragile cable elements. The resin complex stabilizes the cable to prevent decabling during winding. The resin burns out and the glass component vitrifies during

the reaction bake of the Nb_3Sn coil to form a strong, inelastic matrix. The matrix supports the strands and prevents stress concentrations within the cable, fuses the E-glass tape to the cable, and electrically insulates each strand's surface. The ceramic component has a large heat capacity at 4.2 °K, contributing substantial stability against microquenches, and mechanically reinforces the glass after vitrification. The glass/ceramic mix does not fill the space between cable elements, but instead leaves an open porosity within the coil package for liquid helium to bathe the coil throughout similarly to B-stage for NbTi coils. These properties should provide an ideal basis for achieving mechanical support, electrical insulation, and thermal conduction within a Nb_3Sn coil.

We propose a multi-year R&D program, aimed to develop and test magnets of the above designs. The program couples calculations and simulations of the designs, development of core fabrication technologies, and construction and testing of short model magnets. **We plan to build and test two model magnets per year during the first three years.**

D20/7 @ 4.35K rectangular cable	Central Field (T)	I. L. Field (T)	O. L. Field (T)
6400 A	13	13.35	10.45
7000 A Short Sample	14.1	14.45	11.25
7000 A (Short Sample + 11% Degradation at 140 MPa)	14.1	14.45	11.25

Figure4-1. Overall cross-section and detail of coil configuration for the D-20 Nb₃Sn dipole.

Figure4-2. Completed D-20 coil subassembly prior to reaction bake.

Figure 4-3. 13 Tesla pipe dipole, showing the coils the cores, and the prestress collar.

Figure 4-4. 16 Tesla block-coil dual dipole, showing the rectangular coil structure, the iron housing, and the stainless steel inserts.

Introduction

The cost and performance of a hadron collider are largely determined by the field strength and field quality of its superconducting magnets. The dipole strength determines the circumference of the collider for a given beam energy; the dipole field quality determines the sustainable luminosity and the complexity of correction elements required in the collider lattice. The termination of the Superconducting Super Collider has dramatically demonstrated the need for ever-better technology to minimize the cost and maximize the performance of new high energy research facilities. Better magnet technology is required if we are ever to return to the challenge of an ultimate-energy hadron collider with more realistic cost and higher performance.

Conventional Superconducting Dipole Technology.

All conventional superconducting dipole magnets share a common design philosophy: the magnetic field in the beam tube is produced by a cluster of coil elements which surround the tube closely; the return flux circulates symmetrically around this cylindrical coil cluster and is guided in its circuit by a magnetic steel yoke far removed from the central bore. The field quality and magnet efficiency (ampere turns per Tesla) are determined by the configuration of the coil cluster. This philosophy can produce excellent results for field strengths up to ~ 10 Tesla. Figure 4-5 illustrates a successful 6.5 Tesla magnet - the $\cos \theta$ dipole for SSC²⁷. The frontier of conventional technology using NbTi superconductor is the 2-in-1 magnet for LHC²⁸ - a partially flux-linked $\cos \theta$ dipole pair shown in Figure 4-6.

Nb₃Sn dipole challenges.

As we press upon the high-field frontier, however, it is necessary to change from the relatively robust NbTi superconducting cable to the fragile, wind-and-react Nb₃Sn cable. At the same time, the performance of both the $\cos \theta$ and the superferric configurations deteriorates because the coil package becomes thick compared to the beam tube aperture. Figure 4-7 shows the calculated field distribution in a 4-shell $\cos \theta$ magnet similar to the LBL's 13 Tesla D-20 design. An increasing fraction of the ampere-turns are spent driving flux in circles within the coil package rather than producing field in the beam tube. The closure of field within the coil package produces stress concentrations in the coil package, and patterns of stress which are difficult to pre-load to prevent coil motion. Likewise the thick coil package develops a softer modulus, and precise positioning of coil elements becomes increasingly difficult. Figure 4-8 shows a design for a 13 Tesla superferric dipole, extrapolating the 6.5 Tesla design which was successfully built and tested by the Texas Accelerator Center²⁹, which suffers many of the same difficulties.

The block-coil design.

We have resolved both limitations by cutting the Gordian knot of high-field dipole design: we redistribute the coil to best advantage around the magnetic circuit, simultaneously producing an optimum dipole field in each of two apertures and returning the flux in a short path to achieve maximum magnetic efficiency. Figure 4-9 shows the calculated field distribution in a 16 Tesla

block-coil dual dipole. In addition to producing excellent calculated field quality over a wide dynamic range with minimum amp-turns, it offers a number of practical advantages for construction. All coil elements are arranged in rectangular pancake geometry, which is easy to wind with tight dimensional tolerance. Most coil layers have simple racetrack ends; even for the center layers which must be routed over/under the beam tube, we have demonstrated a simple technique in which they can be wound as racetrack coils and then bent out-of-plane at the ends. The rectangular coil geometry provides a particularly simple and effective means to provide optimum preload within a single laminated steel shell.

The pipe magnet.

During the past two years we have also developed a pipe dipole design, shown in Figure 4-3. The pipe dipole disposes the coil around the entire flux circuit, with the remarkable result that flux flows within the coil as water flows in a pipe. Figure 4-10 shows the field distribution: two uniform dipole regions are created within a suitably deformed toroid. Although the pipe dipole requires ~30% more superconductor than the block-coil dual dipole, it has one unique feature: field lines at the coil boundary are everywhere parallel to the coil surface. As a consequence, it is perhaps the only high-field magnet design which could be built using tape conductor for the inner coil elements without the usual problems of AC losses and multipoles due to a field component normal to the tape surface. The possibility of using tape conductor opens the world of Nb₃Sn tape (twice the critical current density of cable, and suitable for ternary additives to extend high-field j_c), other A15 systems which can only be fabricated on tape (e.g. Nb₃Al for fields to 23 Tesla³⁰), and ultimately perhaps for BSCCO³¹ (~30 Tesla at 10 oK). The pipe magnet has no known fundamental limitations up to a field strength of ~20 Tesla - three times the field of the SSC dipoles. Twenty-five years ago Kruger *et al.*³² demonstrated that compact quadrupoles can be successfully fabricated from tape conductor with controlled geometry on both body and end regions (see Figure 4-11). The pipe dipole may offer the opportunity of revisiting this approach for ultra-high field dipoles.

A block-coil quadrupole for low- β insertions.

We have also applied the block-coil approach to design a high-gradient quadrupole appropriate for use in the low- β insertions for the CERN LHC. The block-coil geometry is well suited to achieve a buildable, optimum geometry for a Nb₃Sn quadrupole. We have designed a symmetric quadrupole of the required aperture, which should produce a gradient of 300 T/m at 4.2 oK. The inner two quadrupoles of the LHC triplet have $\beta_y < \beta_x/4$. The block-coil design makes it feasible to design an asymmetric quad, shown in Figure 4-12, matching this 2:1 ellipse. It should produce a gradient (90% of short sample) of 330 T/m at 4.2 °K. This gradient is a 30% improvement over the best 1.8 °K NbTi designs to date - an improvement which translates directly into luminosity.

Significance for the U.S. high energy research program.

These magnet designs represent what may prove to be a true revolution in collider magnet technology. They uniquely open the possibility of fields of 16 Tesla or beyond for future hadron colliders. The development of a technology base for an ultimate 100 TeV hadron collider was cited as a priority for the U.S. HEP program in the report of the HEPAP Subpanel on Vision for the Future of High-Energy Physics. The need for fundamentally new magnet technology was

similarly highlighted in the report of the recent DPF Workshop on Future Hadron Colliders. The proposed long-term R&D program, a collaboration between LBL, Texas A&M University, and Japan, is the only effort which proposes to address this important frontier. Magnet efforts at Brookhaven are focused on RHIC and on transport lines for LHC; magnet efforts at Fermilab are focused on the Main Injector and on low-beta quadrupoles for LHC; magnet efforts at CERN are of course focused upon the preparations for construction of the LHC ring. **If there is to be a future for hadron colliders beyond LHC, we must engender a sustained, long-term program to develop a better magnet technology.**

We propose such a program. It is a collaboration between LBL and Texas A&M University; we are exploring possible interest at other institutions in joining the collaboration. The goal of the program is to explore alternatives for the superconductor and the coil geometry of collider magnets which would make it possible to at least double the current state-of-the-art performance. The programs at our institutions would focus on two complementary objectives:

LBL: (after D20 testing) block-coil quadrupoles;
Texas A&M: dipoles using block-coil and pipe geometries;

The program of work concentrates on building and testing short model magnets. It is only through such testing that any new magnet technology can be evaluated and matured. To this end, in the dipole program at Texas A&M we set ourselves an ambitious overall goal: **we will build and test at least two prototype dipoles each year.** The rationale for this program and a WBS schedule for the first-year program are presented below. The tentative agenda for the proposed 3-year renewal is:

Year 1:	NbTi block-coil dipole	BT-1
	Nb ₃ Sn block-coil dipole	BS-1
Year 2:	NbTi pipe dipole	PT-1
	Nb ₃ Sn block-coil dipole	BS-2
Year 3:	Nb ₃ Sn tape pipe dipole	PST-1
	Nb ₃ Sn block-coil dipole	BS-3

From the SSC, we propose to assemble a group of some of the finest and most experienced magnet personnel and a complete base of equipment for prototype magnet construction and testing. The personnel are prepared to join us immediately; the equipment is contained among the assets which have been transferred to TNRLC. Texas A&M has allocated a 20,000 sq.ft. high-bay building space which will comfortably house the activity. This combination of people, equipment, and facility uniquely makes it possible to engender a new magnet development activity and begin almost immediately building and testing magnets. It is the only combination which will retain these personnel and this equipment in productive activity to create a future for the U.S. high energy research program.

We will rely upon our collaborators for substantial help in many aspects of the dipole program. LBL will contribute ~6 months of effort by Dr. McInturff to supervise the transfer and re-commissioning of the SSC equipment at Texas A&M. LBL will fabricate all conductor required for the dipole magnet program. LBL will contribute teamwork and leadership in several design areas: persistent current fields, quench simulation, coil end supports, instrumentation³³, and cryostat design. During the first-year program, all model magnets will be tested in the cryostat which is being built at LBL for the D-20 tests; this enables us to defer the decommissioning of the test cryostat and ASST system until late in the first year without delaying the model program.

Figure 4-5. Cross-section of the SSC dipole: 6.5 Tesla, 5 cm bore, 4.2 °K.

Figure 4-6. The NbTi dual dipole magnet for LHC: 8.7 Tesla, 5 cm bore, 2 °K.

Figure 4-7. Calculated field distribution in the D-20 4-shell dipole.

Figure 4-8. Calculated field distribution in a 13 Tesla superferric dipole similar to the 6.5 Tesla design which was built and tested at the Texas Accelerator Center.

Figure 4-9. Calculated field distribution in the 16 Tesla block-coil dipole.

Figure 4-10. Calculated field distribution in a 13 Tesla pipe dipole.

Figure 4-11. A tape-wound quadrupole, built at Brookhaven National Lab in 1966.

Figure 4-12. Asymmetric block-coil quadrupole for LHC low-beta insertion: 330 T/m, 7 cm aperture, 4.2 °K.

A. Common Design Features

In order to get a complete picture of the evolution of the dipole field designs described above, Figure 4-14 shows a succession from the NbTi dipoles for the SSC and LHC, to the D-20 Nb₃Sn dipole, to the pipe dipole, to a block-coil version of the pipe dipole, to a variant of the block-coil pipe dipole, finally to the block-coil dipole. The progression is shown in that order because it is the order in which the designs were invented. While the pipe dipole was the first "new geometry" Nb₃Sn design in our work, we consider the block-coil dipole to be the first practical design in the succession which we propose to build and test in the development program. Several design considerations are common to all of our designs: basic field configuration, aperture, field quality, dynamic range, cable orientation, prestress strategy, and coil insulation.

Superconductor.

We have designed the magnets to use rectangular Rutherford cable, with fine-filament Nb₃Sn/Cu strand, similar to that being used at LBL for D-20. We may use a nickel coating (like ITER) to suppress a.c. losses; it would also provide a diffusion barrier for the "inorganic B-stage" insulation. The SC:Cu ratio is graded through the coil for optimum coil performance.

Basic field configuration.

The magnets of Figure 4-3 and Figure 4-4 share a major departure from the conventional $\cos \theta$ coil configuration: The coil elements are arranged in rectangular pancake coils flanking each beam tube, and a magnetic steel flux return is close-coupled just beyond the boundary of the rectangular coil region. This configuration provides optimum packing density, ease of fabrication, optimum prestress geometry, and a simple basis for tuning field quality.

Aperture.

The aperture required for hadron collider operation has been the subject of intense study for the designs of SSC and LHC. The issues determining aperture requirement were recently summarized at the DPF Hadron Collider Workshop. For a $\sqrt{s} = 40$ TeV hadron collider, a good-field aperture ($\delta B/B < 10^{-4}$) of 5 cm horizontally and 3 cm vertically is typically required. In a $\cos \theta$ dipole, the physical aperture is circular. The block-coil dipole has been scaled to provide a 5 cm cylindrical aperture with 10^{-4} field uniformity. In the pipe dipole, horizontal aperture can be provided with modest impact on amp-turns and overall size, while vertical aperture carries a more serious impact because of the necessity to carry the horizontal prestress load of the coil across the arch of the beam tube cavity in the winding core (see Figure 4-3). Happily this asymmetry parallels the aperture requirements. The 13 Tesla pipe design has therefore been scaled to provide a 5×3 cm² elliptical aperture with 10^{-4} field uniformity.

Dynamic range.

The dynamic range of a hadron collider (full energy/injection energy) is ~10:1 to 20:1. The injection field quality in a $\cos \theta$ dipole is limited by persistent-current multipoles which are created when currents are induced to flow between filaments in a strand as a magnet is ramped in field. This phenomenon is reduced by a factor of 10 in our magnets for two reasons: the conduc-

tor is further from the beam than in a $\cos \theta$ coil, and a magnetic steel pole piece presents a planar boundary above and below the beam tube region. As presented below, this boundary condition strongly suppresses persistent-current multipoles at low field. Both of our designs are designed to produce collider field quality over a 20:1 dynamic range.

Cable orientation.

In both of our designs, the cable elements are oriented so that the face of the Rutherford cable is parallel to the field axis. The parallelism is most dramatic for the pipe dipole (Figure 4-10). This provision provides a substantial reduction of AC heat losses when the magnets are ramped during acceleration. AC losses result mainly from currents which are induced to flow between strands within each cable element. Because the cables present their thin dimension to the magnetic flux, induction is minimized for a given inter-strand resistance. This benefit is in marked contrast to $\cos \theta$ designs, where most cable elements are oriented face-on to the magnetic flux.

AC losses.

As a collider magnet is ramped from injection to full field, eddy currents are induced between strands within a cable. The ac losses due to these resistive currents pose a limit to the rate at which a magnet can be ramped. In the DPF Hadron Collider Design Study, ac losses were projected to be a problem limiting performance of ultimate-energy colliders.

In both the block-coil dipole (Figure 4-9) and pipe dipole (Figure 4-10), the cable elements are oriented edge-on to the magnetic field. By contrast, in a $\cos \theta$ dipole the cable is oriented face-on to the field (Figure 4-7), and the field fringes strongly through the coil. The ac losses scale approximately with the projected width of the cable perpendicular to the field direction, so ac losses should be a factor of ten smaller than in $\cos \theta$ magnets. The actual ac losses will also depend on the inter-strand resistance. As part of our cable insulation system development, we plan to try to achieve a high-resistance coating on the strands without compromising j_c performance, using a thin Ni plating, similar to that being developed for the ITER conductor, wetted by the vitreous glass during reaction bake.

Prestress strategy.

As we design dipoles for 16 Tesla and beyond, and use brittle Nb₃Sn conductor for their coils, a primary challenge is to provide a sufficient preload to counter the Lorentz forces without unacceptable coil motion. The rectangular pancake coils of our designs accommodate a particular simple and effective prestress strategy: horizontal pistons from each side, and no necessity of an interleaved collar. The cable elements are oriented face-on to the preload forces, providing the stiffest possible modulus against coil motion.

Coil insulation.

Even with the elimination of stress concentrations, the Lorentz stress at 16 Tesla is immense - 170 MPa. We plan to develop a new approach to Nb₃Sn cable insulation; an "inorganic B-stage", which would provide micro-quench stability and inter-strand mechanical support. The approach is described in Section 5 and illustrated in Figure 4-13. It is similar to work done by Ceramphysics and Westinghouse²⁰, by Tanaka *et al.*³⁴, and by Schutz and Reed³⁵, in that it uses a glass/ceramic mixture to coat the strands of each cable element, providing both mechanical sup-

port and electrical insulation. It is different from both of the previous approaches in that the insulating mixture is applied in a green state in the cable before winding, in such a way that the final insulation (after the Nb₃Sn reaction bake) leaves open porosity in the spaces between cable elements. Liquid helium permeates this space, bathing the coil and providing enhanced enthalpy to stabilize against microquenches. Two experts in inorganic composite systems are collaborating with us to develop an optimum mixture which achieves this combination of properties.

Coil winding strategy.

In both designs, most coil elements are in the form of simple rectangular pancake coils, and can be wound as a racetrack in a particularly simple manner. The central coil elements which flank the beam tubes must be bent up and over the beam tube at each end, however. Historically the techniques for fabricating the ends of a coil are the "weak link" in the entire fabrication operation, and produce the highest likelihood of failure in the finished magnet.

We have devised a technique for winding racetrack coils, in which the entire coil package is completed as a flat pancake coil, and the ends are then bent up *as an assembly*. Figure 4-15 shows a mock-up coil of Nb₃Sn cable which has been wound flat, then bent as an assembly to clear a 5 cm. Beam tube. A very modest force is required (~10 N), and there is no damage whatever to the coil or its E-glass insulating sleeve. Two things happen in this approach which are actually helpful in preparing the end coil for collaring and prestressing. First, as seen in the picture, the geodesic of the bent coil actually flares out slightly, forming a hoop of somewhat larger radius than the actual inner spacing of the body coil. This both relieves the stress concentration which would otherwise occur at the interface between body and end regions, and reduces the magnetic field in the end coil. Second, the turns tend to pull together, removing the slight slack between turns in the end region, so that the bent coil end assembly is tight and forms an integral block to collar and prestress.

By using this simple, effective winding technique, all coils for the block-coil magnet can be wound as flat racetrack assemblies, and the central coil segments can be bent up as required. The winding process should be simple and amenable to precise dimensional control. For the pipe dipole, the coil in the toroidal region is comprised of fan coil segments, each of which is a 3:1 fan from a single inner layer to three contiguous outer layers, as shown in Figure 4-16. The coil segments for the dipole region would be fabricated using pancake coils as discussed above.

Nb₃Sn presents substantial challenges in fabricating long dipole coils. Because the coils must be reacted after winding, the coil must be configured for the ~750 °C bake in a support fixture which matches closely the expansion of the cable. Figure 4-17 illustrates this problem in the case of D-20. Each coil section was wound tightly upon the end spacers as the layer was successively wound. In the bake, however, differential expansion between the (Al bronze) end spacers, the (Cu) body spacer, the base fixture, and the cable produced a relative elongation of the coil as temperature increased followed by a contraction as it decreased. Friction and the stiffened modulus of the coil after reaction apparently prevent the process from reversing itself during cooldown, leaving gaps in the coil/support space. Such gaps are not necessarily a problem, if one stuffs the gaps with fiberglass wadding and then impregnates the coil as LBL does. Since we plan to strive to achieve an "inorganic B-stage" insulation (see below), such gaps are more serious.

Figure 4-13. Schematic illustration of inorganic B-stage insulation strategy.

(a)

(b)

(c)

(d)

(e)

(f)

Magnet	Field Strength (T)	Store Energy (MJ/m)	Amperturns (MA)	Size (mm)	b2 (unit)	
					@injection	@collider
a. SSC dipole	6.5	0.105	0.585	O 330	2	2.0
b. LHC dipole	8.65	0.548	1.88	O 560	3	2.5
c. Berkeley D20	13.0	0.862	1.72	O 820	N/A	N/A
d. Pipe magnet	13.0	3.64	5.50	860*760	N/A	1.8
e. Hybrid magnet	13.0	2.23	4.50	O 500	N/A	2.0
f. Block magnet	16.0	4.36	5.39	O 500	0.4	-0.23

Figure 4-14. Evolution of dipole design, from $\cos \theta$ to pipe to block-coil. The parameters for the dual-aperture designs (b, d-f) are for both bores together.

Figure 4-15. Photographs of a mock-up coil of Nb₃Sn cable, in which the entire coil end has been bent up to clear a 5 cm beam tube.

Figure 4-16. Schematic illustration of the winding arrangement for one toroid coil segment.

Figure 4-17. Photograph of an inner coil of the D-20 magnet, after reaction bake.

B. Block-Coil Dipole

The block-coil dual dipole is configured as a window-frame magnet, in which the coil is divided into three segments so that the Nb_3Sn conductor can be graded to optimize $j_c(B)$. Figure 4-18 shows the load line for the three coil segments, designed to optimally utilize the superconductor throughout the coil.

Field quality and dynamic range.

The multipole content is dominated by two phenomena: the pairing of the two dipoles introduces an asymmetric reluctance which in turn produces a quadrupole; and the progressive saturation of the steel produces a sextupole and decapole. We have corrected these effects by introducing three modifications. First, the innermost coil is arranged on a contour which cancels the decapole and some of the sextupole (Figure 4-19). Note that the contour is antisymmetric: the coil profile is shaped on the inner boundary of the inner leg, and the outer boundary of the outer leg in each dipole.

Second, the three coil elements are gapped apart asymmetrically, to correct the reluctance asymmetry. The coils are spaced with minimum gap on the outer leg, but with substantial spacers on the inner leg. This cancels most of the quadrupole. shows the calculated multipoles which result when all three coils, thus configured, are excited by a common (series) current. While it is possible to achieve collider-quality field at full excitation, at low field substantial quadrupole (~ 40 units) and sextupole (~ 40 units) fields are produced, due to the transition of the steel from unsaturated to saturated state as field is increased.

The third modification is to operate the three coil segments with different currents. The currents can be programmed to cancel all multipoles to less than one unit (10^{-4} cm^{-n}) at all field strengths over a 20:1 dynamic range. Figure 4-20 shows the current programming $I_i(B)$. Figure 4-21 shows the multipole content as a function of field strength.

The choice of aperture is governed by several considerations. The aperture requirement for collider operation has been the subject of exhaustive scrutiny throughout the design of SSC and LHC. The subject was reviewed at the recent DPF Hadron Collider Workshop. The horizontal aperture requirement is dominated by the dispersion due to momentum spread at injection; for SSC it was 5 cm. physical aperture, 3 cm collider-quality field. The vertical aperture does not require accommodation of momentum dispersion; the same 3 cm. collider-quality field aperture suffices.

Persistent-current multipoles.

Two of the virtues of both the block-coil and pipe designs is the suppression of magnetization fields by the planar steel boundary, and the suppression of a.c. losses by the orientation of the cable elements edge-on to the field. We have calculated the multipole fields produced by magnetization currents within the superconducting strands, following the procedure of Caspi³⁶. Each coil segment is represented by a magnetization block, with a M/H magnetization curve appropriate to describe the measured magnetization properties of the actual superconducting strand.

This approach has been used to accurately reproduce the observed magnetization fields in Tevatron and SSC magnets. For Nb_3Sn cable, the filament size represents a somewhat uncertain parameter in estimating the magnetization curve: while the intrinsic filament size in the internal-tin strand which is used at LBL for D-20 is quite small ($\sim 2 \mu\text{m}$), the diffused tin between strands produces a weakly superconducting bridge at low current and field, equivalent to a much larger "effective strand size" at injection field. The low-field effective strand size is estimated to be $\sim 20 \mu\text{m}$ for the material currently in use. A magnetization curve appropriate for that strand size was adopted for our calculations.

Figure 4-21 shows the persistent-current multipoles calculated for the 16 Tesla block-coil dual dipole. The maximum sextupole hysteresis is ~ 3 units at $B_0/20$, one tenth of the b_2 at the same fraction of full field for an SSC dipole (Figure 4-22). We have included the calculated magnetization fields in a re-optimization of the current programming, and can again reduce all multipoles to < 1 unit over the full 20:1 dynamic range (Figure 4-24).

Current programming.

The block magnet requires current programming to achieve optimum field over a 20:1 dynamic range. We realize that current colliders utilize a single current bus for the main dipole family, and that many in the accelerator community have strong opinions that multiple current busses would pose a major risk to stable operation. Certainly a number of issues arise which must be evaluated quantitatively before a multiple-bus scheme could be seriously entertained for a future collider. However, all of the issues we have been able to identify appear to be readily manageable without substantial cost or risk.

The frequently cited need for independently adjustable orbits can be accommodated at the level it is required by means of a family of lumped correction elements in the spool pieces. The power supply stability and regulation requirements are well within commercial power supply technology. The quench protection design must be segmented in multiple parallel circuits for diode clamps, dump resistors, and heaters, so the segmentation would actually be a convenience. The accommodation of multiple current busses in the cryostat is a modest issue in the overall design. The only issue which we have identified which appears to need some near-term analysis is the potential for transmission-line modes propagating around the magnet ring, in effect shunting current among the three circuits in a differential traveling wave which might propagate with little attenuation.

Quench protection.

With a stored energy of 2.2 MJ/m in each dipole, quench protection is a critical consideration for reliable magnet operation. From the experience to date with quench protection of collider dipoles, the parameter which is of great importance in quench dynamics is the maximum current density j_{Cu} which would appear in the copper stabilizer of the cable during a quench. If $j_{\text{Cu}} < 1,100 \text{ A/mm}^2$, active quench protection can usually be designed to safely distribute a quench so that a magnet consumes its stored energy without overheating at any location. If j_{Cu} exceeds that limit, quench protection is usually very difficult, particularly for distributed strings of magnets which must be effectively isolated from one another so that a quench does not propagate from magnet to

magnet. We have adopted this limit in designing the SC:Cu ratio for all coil segments in our designs. Table I presents the parameters of all three coil segments in the block-coil dipole.

We are currently simulating the quench behavior of the block-coil magnet, using a modified form of the code QULHC³⁷. We have assumed a network of clamp diodes, limiting and dump resistors, and pulsed heaters as shown in Figure 4-25. The quench is assumed to initiate on an inner coil segment. The decay of current during the quench is shown in Figure 4-26; the decay time constant is ~ 0.2 sec. Figure 4-27 shows the total coil voltage (resistive plus inductive) across each coil segment during the quench. A maximum of 1,300 V is developed; the maximum voltage location is on the middle coil under the initiation condition studied. Figure 4-28 shows the maximum temperature as a function of time during the quench. A maximum of 430 °K is reached on the outer coil. These results are only the beginning of our study of quench dynamics in the block-coil dipole. The circuit parameters in Figure 4-25 have not been optimized, and the limits in temperature and voltage can probably be improved. We are experimenting with the segmentation and placement of circuit elements to that end. These preliminary results are already within reasonable bounds for a localized, non-destructive quench. They demonstrate that the 16 Tesla block-coil dual dipole can be adequately protected.

Prestress Strategy.

The total preload on each side required to counteract the Lorentz force is $F = S w = 22$ kT/m. The preload must be delivered to the side wall of each coil assembly. In this respect the block dipole is ideal for simple, effective preloading. Figure 4-25 shows two techniques for delivering the preload. The simplest approach is to divide the steel flux return at the top and bottom of its rectangular cavity, creating two pistons on the sides. The pistons are then pressed inwards in a press to the desired preload, and the outer seams between the pistons and the top/bottom pieces are welded to lock in the preload. It is hard to imagine a simpler way to deliver a controlled preload. The one disadvantage is that some fraction of preload would likely be lost in cooldown, due to differential contraction.

The second approach uses the differential contraction of Al and steel to advantage to deliver additional cold preload, in a fashion similar to that used at Brookhaven, SSC and CERN. The steel flux return is segmented at the bifurcation between the region where flux couples between the dipoles and the region where flux returns on the outside leg. In this way one eliminates any effect on field strength or homogeneity from any residual crack at the interface. A controlled gap is made between the steel segments, and bars of aluminum are placed at the top and bottom of the assembly to space the gap while the magnet is at room temperature. When the magnet is cooled to 4.2 °K, the Al bar shrinks more than the steel, and the gap closes, delivering additional preload to the coil. The preload would be delivered in this strategy by either banding or wire-wrap around the steel assembly.

Table 1. Superconductor properties in the coils of the block-coil dipole.

	inner coil	middle coil	outer coil	
effective filament diameter	20	18	18	μm
# filaments	1164	933	1289	
strand diameter	0.965	0.825	0.980	mm
# strands	34	19	13	
Cu/SC	1.0	1.15	1.3

Figure 4-18. Load line for the three coil segments of the 16 Tesla block-coil dual dipole.

Figure 4-19. Calculated multipoles in the block dual dipole: all coils operated in series.

Figure 4-20. Current programming of three coil currents to produce optimum field quality.

Figure 4-21. Calculated multipoles in the block dual dipole with current programming.

Figure 4-22. Calculated persistent-current multipoles from magnetization fields.

Figure 4-23. Measured persistent-current multipoles in SSC prototype dipoles.

Figure 4-24. Residual multipoles after re-adjusting the current programming to cancel magnetization fields.

Figure 4-25. Circuit used in simulation of quench protection for block dipole.

Figure 4-26. Current decay during quench in each coil segment.

Figure 4-27. Coil voltages during quench.

Figure 4-28. Maximum temperature in each coil during quench.

Figure 4-29. Two techniques for applying preload to the block dipole: a) side bars acting as piston; b) split flux return along flux bifurcation, and insert Al spacer for cold preload.

C. Pipe Dipole

The pipe magnet consists of two current sheets, configured roughly as a toroid, with insertions which produce a high-quality dipole field at two opposite locations for the two beams of a hadron collider. The design strategy is summarized in Appendix D. The real "magic" of the pipe magnet is the invention of a **flux transformer** which changes the field $\vec{B} = B_0(R/r) \hat{\phi}$ of the toroid sections into the uniform field $\vec{B} = B_0 \hat{z}$ of the dipole section. We have invented a particular deformation of the outer current sheet which produces the desired transformation²⁶. The collider field quality can be readily achieved in the dipole insertion without additional corrections. Addition of a modest pole face winding at the boundaries of each dipole section could be used to further reduce or tune multipoles.

Field optimization

Design of the pipe dipole has required both the use of a new software environment, OPUS, to optimize the geometry for the flux transformation, and a rather intricate meshing of the 2-D structure to adequately model the structure. Figure 4-24 shows the finite-element mesh which was used in PE2D to calculate the magnetic field distribution and forces.

Figure 4-10 shows the calculated magnetic field distribution for such a coil configuration. The optimization produces the following approximate guidelines:

- the mean radius of the toroid sections should be $\sim 5a$, where a is the radius of the beam aperture within which uniform field is required in the dipole section;
- the coil in the toroid section should have an integral ratio (typically 3:1) of outer to inner radius, in order to accommodate the flux transformer;
- the transition from dipole to toroid should include a tapering of current distribution, from the one limiting case to the other, with a modest flux leakage in the transition which must be compensated in the magnetic design.

Table 2 presents the calculated multipoles for the 13 Tesla pipe dipole. The design assumes cable conductor, similar to that used in D-20, with 3 graded current densities through the thickness of the coil. All 3 coil segments are assumed to be operated in series. A pole-face winding has been included at the interface between the center dipole insert and the U-shaped toroid inserts, in order to provide tuning of multipoles below the 10^{-4} cm⁻ⁿ level. No analysis has yet been made of the error fields which would result from conductor placement errors. Such analysis will of course be necessary before arriving at a prototype design.

Figure 4-30. Mesh for numerical modeling of the pipe dipole in PE2D.

Table 2. Calculated multipoles of the 13 Tesla pipe dipole

n	$b_n (10^{-4} \text{ cm}^{-n})$
1	-.004
2	-.63
3	+.023
4	-.17
5	+.064
6	-.48

Tape conductor for the pipe dipole.

The pipe dipole is unique in the feature that the magnetic field in its bore circulates around the internal region, and does not fringe through the coil package. Comparison of Figure 4-10 with all of the other field geometries above shows that, uniquely in the pipe magnet, the magnetic field at the location of the conductor is everywhere tangential to the boundary of the coil package. If the coil were to be fabricated from tape conductor, there would be very little field component normal to the face of the tape. This feature is crucial to the possibility of building superconducting dipoles using tape conductor. While such dipoles have never been developed (although Figure 4-11 shows a tape-wound quadrupole from 25 years ago), they would open the world of inexpensive conductor fabrication for Nb_3Sn , and perhaps of practical conductors using high-field A15 systems and BSCCO.

The limiting consideration in using tape conductor is magnetization current which would be induced by time-changing magnetic flux through the face of the tape. In a tape-conductor pipe magnet, the flux would be oriented parallel to the tape face, and such currents would be largely avoided. This feature is vital from the consideration of j_c , field quality (persistent-current multipoles), and a.c. losses. Figure 4-27 presents data³¹ on the effect of magnetization currents in BSCCO tape if the magnetic field forms a significant angle α with respect to the tape-normal direction. j_c would be degraded by a factor of 3 if tape conductor were used in a $\cos \theta$ dipole ($\alpha \rightarrow 0^\circ$ at some regions of inner coil), by a factor of ~ 1.4 in a block-coil dipole ($\alpha \rightarrow 70^\circ$), and not at all in a pipe dipole ($\alpha = 90^\circ$ everywhere).

Current requirements.

The pipe dipole requires 5.5 MA turns of conductor, a little more than the block-coil dual dipole. If it proves feasible to use tape conductor, the actual mass of superconductor may be significantly reduced, however, since the high-field critical current in tape is typically $\sim$ twice as great for Nb_3Sn tape as for cable. The aggregate conductor mass would be governed mainly by the amount of Cu required for realistic quench protection.

GE has developed a continuous tape fabrication process for Nb_3Sn tape, and plan to work with LBL to develop and evaluate tapes with ternary alloys and artificial pinning centers (APC). Their process is a continuous-feed fabrication, beginning with a Nb (or NbTa, etc.) ribbon, which is coated with Sn in a dip process, then reacted in a fast high-temperature continuous-feed furnace, then clad to Cu stabilizer and insulating layer. The unit cost for fabrication of large quantities of conductor with this process is unknown, since it is now being used for a product for the first time - a 1 Tesla split solenoid for MRI during surgery. It appears likely, however, that Nb_3Sn tape conductor could prove to be substantially less expensive and higher performance than an equivalent cable.

Tape is the only process by which high-field, high- j_c performance has yet been achieved in Nb_3Al . Figure 4-25 shows the measured short-sample j_c for Nb_3Al tape which was fabricated using each of two continuous processes³⁰ in which the reaction is achieved using a laser and an electron beam, respectively. In both cases, $j_c \sim 200 \text{ A/mm}^2$ at 4.2 °K was achieved, with maximum field of ~ 23 Tesla.

Tape remains the best form in which to achieve high j_c and high B_c in practical high-temperature superconductors (HTS) such as BSCCO. Because the HTS mechanism involves conduction along ordered planes in the perovskite structure, orientation of grains in a continuous layer is of critical importance. This is more readily achieved in tape form than in wires. Figure 4-26 presents measured j_c vs. B for BSCCO tape³¹; $j_c \sim 200 \text{ A/mm}^2$ up to ~ 30 Tesla at 20 °K. The possibility of operating at higher temperature could become an important feature at an ultimate-energy hadron collider, because the synchrotron-radiation heat load will likely dominate the heat budget, and could dominate the entire power budget of the facility.

Prestress strategy.

Figure 4-28 shows the calculated pattern of Lorentz stress in the coil package of the 13 Tesla pipe dipole. The stress concentrates in the dipole coils, and drops by a factor of 10 in the

toroidal regions. We have designed a prestress strategy which delivers a compressive preload in this pattern. A banding of either high-strength tape or wire is wrapped around the pipe dipole assembly as shown in the figure. A piston, located on each side of the assembly, serves as a load concentrator. The capstan force delivered by the banding in any region is proportional to the arc angle subtended by the tape as it bends around the region. By shaping the pistons as shown, most of the arc angle (hence most of the compressive force) can be concentrated in the two side pistons and delivered to the dipole regions. We have done some preliminary finite-element modeling of the piston and the distribution of preload around the coil assembly. It appears to be feasible to match it fairly closely to the pattern of Lorentz stress.

Some experts have criticized this prestress strategy, on the basis that several prototype $\cos \theta$ dipoles were fabricated with wire-wrapped preload in the early phases of the Tevatron magnet R&D, and the magnets twisted uncontrollably after the assembly was released from the banding fixture. In our opinion, this result was predictable for the $\cos \theta$ geometry but irrelevant for the pipe geometry. In a $\cos \theta$ geometry, there is very little internal structure to the magnet. The structure is provided almost entirely by the collar assembly. Thus if one replaces the stack-weld lamination assembly by a wrap of banding, there is nothing to maintain alignment in a long magnet. By contrast, a pipe magnet has a massive internal structure, in the form of its magnetic and non-magnetic laminated cores (see Figure 4-3). This structure should provide excellent alignment integrity for a long magnet, independent of the means used to deliver preload. We note in closing that LBL has decided to use wire-wrap to deliver preload to the D-20 prototype, in which the steel shell can provide alignment integrity.

Figure 4-31. Short-sample measurements of j_c vs. B for Nb_3Al tape conductor.

Figure 4-32. Measurement of j_c vs. B in BSCCO tape.

Figure 4-33. Dependence of j_c on the angle between B and the tape-normal direction.

Figure 4-28. Distribution of Lorentz stress in the coil assembly of a 13 Tesla pipe dipole. Peak stress is 100 MPa.

D. Block-Coil Quadrupole for Low- β Insertions

One of the most challenging magnet design requirements for CERN's LHC is the low- β insertion at which the beams collide at high luminosity for each experiment. Attaining high luminosity requires that the beams be squeezed to the smallest feasible focus. Taylor³⁸ has designed an inner quadrupole triplet insertion which would produce $\beta^* = 0.5$ m at the intersect. The design is shown in Figure 4-29. It requires quadrupoles with an aperture of 70 mm and a gradient of 250 T/m. Design efforts have been undertaken at CERN, Fermilab, and LBL to design cos 2 θ quadrupoles which would meet this requirement. It is at the limit of feasibility with NbTi, even at 2 °K. Such designs are problematic for two reasons. First, the inner quads will receive a heavy load of energy deposition from lost particles; the heat must be conducted through the coil, creating a temperature differential which would be especially problematic at 2° K. Second, most such designs have to push the SC/Cu ratio in the cable to problematic limits; the current density j_{Cu} which would appear in the Cu stabilizer is $\sim 1,300$ A/mm² in several such designs, beyond the capability of readily achievable quench protection strategies.

We have applied the same block-coil approach to design a block-coil quadrupole, using Nb₃Sn superconductor at 4.2 °K. It produces 300 T/m gradient (90% short sample), with an circular aperture of 70 mm. Figure 4-30 shows the calculated fields in the magnet. The block coil is oriented appropriately for relatively simple winding strategy. The cables are face-on to the direction of preload, providing a stiff modulus. The side boundaries of each coil segment are appropriate for mounting of a heater strip in excellent edge contact to all turns of the coil, assuring optimum rapid distribution of a quench using pulsed heaters. The 4.2 °K operation provides some margin for heat transport for beam losses; indeed the $j_c(T)$ for Nb₃Sn decreases more slowly with temperature than it does for NbTi.

With the block-coil approach, it is straightforward to design an asymmetric quadrupole. In the lattice of Figure 4-29, the beam envelope is asymmetric through the most critical elements (where the beam has largest size), $\beta_y \sim \beta_x/4$. The beam envelope is thus twice as wide as it is tall through the middle magnets of the triplet. We have designed a 2:1 asymmetric quadrupole to provide the highest feasible gradient in that region. Figure 4-12 shows the calculated fields. It provides 330 T/m gradient - 30% more than the LHC lattice requires. This design example illustrates again the power of the block-coil approach to design a buildable, optimal solution to a wide variety of magnet design requirements.

Figure 4-35. Low- β insertion for LHC. Note that $\beta_y \sim \beta_x/4$.

Figure 4-36. Symmetric block-coil quadrupole: 300 T/m gradient, 70 mm aperture, 4.2 °K.

E. Inorganic B-stage for Nb₃Sn Coil Insulation

In Nb₃Sn magnet technology, the strand or cable elements are wrapped with E-glass or S-glass cloth, either as a half-wrap or as a tubular sock. The coil is baked in a reaction bake cycle (~24 hour, 750 °C, inert atmosphere) to diffuse the Nb and Sn in the heterogeneous strand composition to form superconducting Nb₃Sn filaments. This process must be done after winding (wind-and-react) because the superconducting alloy is brittle and subject to fracture in winding and forming operations. The glass cloth cable insulation is typically impregnated with sizing (e.g. starch, ~2% by weight) to make it pliable for handling. The starch is burned out in an atmospheric bake to 400 °C prior to the reaction bake.

Immediately after the reaction bake, the coil is vacuum impregnated with an epoxy system; the impregnated coil is then cured to produce a solid composite. There are three good reasons for the vacuum impregnation. First, the glass cloth becomes extremely brittle after the sizing is burned out, and is prone to fracture. Second, the glass cloth can prevent cable-cable shorting, but cannot prevent electrical breakdown in He gas during a quench (the Paschen limit ~1,000 V). Intra-coil breakdown could damage the coil and its insulation. Third, the strands within a Rutherford cable must be supported by a matrix in the space between them, or the prestress forces would crush them at the points where strands pass over one another in the transposition pitch of the cable. At those locations the macroscopic preload would produce a stress concentration, which would yield the strand matrix and fragment the superconducting filaments, degrading j_c . The impregnated epoxy provides support in the inter-strand space so that stress does not concentrate.

The impregnation of a coil brings with it an unfortunate problem. Liquid helium is excluded from the coil, and cooling can only be provided at the coil boundaries. For a thick coil, heat produced in the coil must transport through the rather poorly conducting epoxy/glass matrix to be removed. Even a modest heat load could produce a significant temperature differential within the coil. In a typical collider magnet, two major heat sources are intimately associated with the coil: synchrotron radiation is absorbed on the beam tube, and beam losses produce energy deposition directly in the coil. These heat sources become more of a problem as the collider energy increases. Inclusion of additional materials in the epoxy/glass impregnation usually only makes the problem even worse. For example, the CERN group tried using mica as an inter-coil insulation. The mica developed microscopic voids between the lamina of the crystal structure, which caused its thermal conductivity to decrease tenfold.

What is needed is an insulating system which provides a solid support matrix in the inter-strand spaces within a cable element, and forms a dielectric coating on all strand surfaces to block gas breakdown during quench, and stabilizes the glass cloth wrap, but provides an open porosity within which liquid helium can flow in the (thin) gaps between cables in the coil package.

We propose to develop such a system. Several authors have developed similar insulation strategies^{34,35} is illustrated in Figure 4-13:

- A fluid composite of ceramic and glass powders, resin, and volatile vehicle is used to impregnate the cable and possibly the E-glass tape as well. Each is dried to remove the volatile vehicle, and to cure the resin if necessary;
- The tape is half-lap wound onto the impregnated cable,
- The insulated cable is wound onto the coil forms to fabricate the coil package;
- The ends of the inner layers are flared as described above;
- The completed coil is fired to remove all organic resins and sizing, then baked to react the Nb₃Sn.

The glass-ceramic-resin material must satisfy a number of criteria in order to provide the necessary functions described above. The liquid material must be capable of penetrating the cable in a dip process to fill the interstices between strands. The dried and cured material must adhere to the strands, and provide a flexible, cohesive bond to prevent decabling when bending the inner coil ends. The glass-ceramic mix must wet to the surface of the strands during the reaction bake, must not diffuse into the strands to a degree which would poison the superconducting performance of the Nb₃Sn alloy, and must form a tough matrix of very hard modulus after the reaction bake is completed. The mix must bridge the spaces between strands sufficiently to eliminate stress concentrations under face-on cable loading. The mix must form a continuous, vitreous coating on the strands to provide electrical isolation from the liquid helium. The voids left following the burnout of the resin (~50% of the mix by volume) must form an open matrix which permits penetration of liquid helium throughout the coil package.

Two lines of development are pertinent to a technical solution to these multiple demands. First, Ceramphysics has developed several glass-ceramic formulations in which the ceramic component provides large heat capacity at liquid helium temperature and reasonable thermal conductivity. While the ceramic component does not sinter at the ~750 °C reaction temperature of the cable, several glasses were used which vitrify at that temperature and provide a continuous matrix which incorporates the ceramic powder and wets to the cable strands. It was found that wetting required that a layer of nickel be electroplated on the strand surface. Nickel poses a diffusion contamination for Nb₃Sn, however, so it is suggested that the chromium plating which is being done for the ITER project may serve the same function of promoting wetting of the glass while also providing a diffusion barrier against any poisoning of the strand by components of the ceramic-glass mix.

Second, Ferro has developed a product line for thick-film technology which uses resin resin filled with ceramic and glass powders to produce a stable film for electronic substrates. If a suitable mix of glass and ceramic powders could be formulated in their resin resin, the above combination of properties might be achievable.

The overall process that is desired is akin to the "B-stage" process of epoxy impregnation for NbTi superconducting magnets (which do not require a reaction bake), in which green epoxy is loaded into a tape, wrapped onto the cable, and the completed coil is reacted to cure the epoxy while leaving porosity for helium penetration. A third company, Composite Technology Development, has developed processes of this sort and has committed to collaborate with us to develop the inorganic B-stage. They have a well-equipped test lab and can test most mechanical, electrical, and thermal properties of interest.

In order to achieve success with the proposed insulation strategy, it may be necessary to employ two seemingly disparate concepts, either separately or in concert. One concept uses binders, capable of carrying high loading of inorganic fillers, that can be thermally decomposed with near-zero char formation. The other concept is to use "pre-ceramic" polymers that are capable of being thermally decomposed at temperatures $< 175^{\circ}\text{C}$ to form amorphous inorganic compounds with useful dielectric insulating properties.

With either concept it will be necessary to control the removal/decomposition of the resin carefully to assure that sufficient structural integrity, porosity, and coating of the individual cable strands are obtained. The important parameters to be controlled during thermal processing will include time, temperature, and the furnace atmosphere.

Low-char organic resins.

Two classes of low char forming resins will be considered: resins that decompose in air or oxygen-enriched atmosphere to give the typical volatile combustion products; and resins that will thermally degrade to form volatile organic products, usually the monomers from which the resins were originally made.

Resins susceptible to low temperature combustion.

Some candidate polymers to be considered as resin systems for the glass/ceramic insulation are listed below with comments:-

- Poly(vinyl alcohol), PVA, $[-\text{CH}_2-\text{CH}(\text{OH})-]_n$ - water soluble; capable of containing high loading of inorganic oxides; used to slip cast barium titanate ceramics.
- Poly(vinyl acetate), PVAC, $[-\text{CH}_2-\text{CH}(\text{OOCCH}_3)-]_n$ - probably capable of containing high loading of inorganic oxides.
- Poly(acrylic acid), PAA, $[-\text{CH}_2-\text{CH}(\text{COOH})-]_n$ - water soluble, very compatible with inorganic oxides, large technology base.
- Poly(ethylene oxide)/poly(ethylene glycol), PEO/PEG, $[-\text{CH}_2-\text{CH}_2-\text{O}-]_n$ - water soluble; forms complexes with metallate ions, compatible with inorganic fillers.
- Natural rubber latex emulsion (water) - very susceptible to oxidative degradation at relatively low temperatures, should be able to make suspensions with fine inorganic oxide powders and appropriate surfactants and dispersing agents.
- Poly(isobutylene), $[-\text{CH}(\text{CH}_3)_2-\text{CH}_2-]_n$ - low char forming polymer.
- Dow Chemical XUS-40303.00 high burn out binder, undisclosed composition; water and organic solvent soluble; used for ceramic fabrication as a "green" binder.

PVA, PVAC, PAA, and PEG all contain a high oxygen content ($C/O = 2/1$) to promote complete combustion under oxidizing conditions. This should facilitate the removal of the resin during burnout in air at elevated temperatures. For example, Union Carbide's Carbowax® PEG 20M is reported to leave an ash of only 0.05% theoretical during thermogravimetric analysis (TGA) in air to 375-400 °C. Because they are all polar polymers, they are compatible with inorganic compounds and should be able to handle high loading of filler compounds and still remain feasible.

The use of an elastomeric binder such as a natural rubber latex (in emulsion form for easy impregnation) or poly(isobutylene) which remains a liquid at room temperature when the formula weight is between 300 and 3,000 is potentially beneficial because it could lead to a more ductile cable assembly prior to burnout. The complete degradation of latex rubber is promoted by ozonolysis which promotes the breaking of C-C bonds. Thus it may be advantageous to use an ozone containing air atmosphere to facilitate the low temperature removal of elastomeric resins.

Dow Chemical's high-burnout binder, XUS-40303.00 is of interest, since it is designed to be used as a "fugitive" binder in the first stage preparation of monolithic ceramic shapes. It reportedly melts at 110-120 °C and undergoes a catastrophic decomposition at temperatures of 350-750 °C with a 99% weight loss.

Resins that pyrolyze with little or no char formation.

A number of readily available polymers thermally decompose essentially completely into volatile decomposition products. Most of these decompose by unzipping of the polymer chains to regenerate the volatile monomers. Some potentially useful pyrolyzing polymers are:

- n Poly(methylmethacrylate), PMMA, $[-CH_2-C(CH_3)(COOCH_3)-]_n$
- n Poly(alpha-methyl styrene), PMS, $[-CH_2-C(CH_3)(C_6H_5)-]_n$. These two polymers unzip completely at elevated temperatures in inert atmospheres with 100% regeneration of the volatile monomers.
- n Nylon 66 (polyamide) is interesting because it yields no char when it is combusted in air. Since one would expect at least moderate amounts of char from aerial thermolysis of a polyamide polymer, it likely at least unzips in part.
- Poly(dimethylsiloxane), PDMS, $[-Si(CH_3)_2-O-]_n$ polymers are commercially available with a wide range of molecular weights. They can be cured at 100-150 °C using conventional peroxide curing agents, and decompose at 600-700 °C without the formation of char. If the decomposition were carried out in air, we anticipate that a significant residue of amorphous silica would remain. A commercial copolymer of PDMS and methylmethacrylate is also available. This material also is expected to be a zero or near zero char former during thermal decomposition.
- Polycarbosilane polymers are being used as pre-ceramic polymers. Dietmar Seyferth, in an overview paper reports that polysilmethylenes, $[-(CH_3)_2Si-CH_2-]_n$, decomposes thermally in an inert atmosphere without the formation of char³⁹. W.P. Weber *et al.*

report two complex polycarbosilanes^{40,41} that when pyrolyzed in nitrogen between 550-750 °C and >450 °C respectively.

Pre-ceramic polymer resins.

Because of the current technical and industrial interest in both electronic and structural ceramic materials, a new technology has developed around the use of pre-ceramic polymers. These are polymeric materials that can be decomposed thermally under moderate to high temperatures to generate useful refractory ceramic materials. In contrast to fugitive (green) binders, when pre-ceramic polymers decompose they are converted in significant part into useful oxide or non-oxide ceramic materials. Much of the technology reported in the open chemical literature and the patent literature deals with the formation of the following crystalline phases:

- SiO_2 ;
- Al_2O_3 ;
- aluminosilicates;
- metal titanates;
- SiC ;
- B_4C ;
- TiB_2 ;
- Si_3N_4 ;
- refractory metal borides, carbides, nitride, and silicides.

Generally the thermal decomposition of the pre-ceramic polymers takes place in two steps. First the polymers are heated at moderate temperatures (<1,000 °C) to decompose the polymer and remove most of the volatile decomposition products and form amorphous ceramic precursor powders. Second the amorphous first stage decomposition products are annealed at sufficiently high temperatures to form the desired crystalline ceramic phases.

We plan to consider a number of pre-ceramic polymers as resins for impregnating the cable segments and the E-glass tape. One objective will be to generate amorphous oxide or non-oxide phases that will provide a structurally intact framework, useful porosity, and satisfactory dielectric properties.

As mentioned earlier, the exact stoichiometry of the amorphous chars, and the conversion efficiencies will depend on time, temperature, and the furnace atmosphere. By decomposing certain pre-ceramic polymers in air or under low partial pressures of oxygen it will be possible to form relatively low melting oxide glasses in relatively high yields. And, of course, it is possible to form glass/ceramic compositions that will form a liquid phase, below 750 °C, especially if certain inorganic glass forming modifiers are dispersed in the impregnating resins. Potential classes of pre-ceramic polymers are:

- Polycarbosilanes
- Polycarbosilazanes

- Silicone resins
- Filled high yield carbon precursor resins

A large number of polycarbosilane and polysilazane polymers have been commercially developed as precursors to SiC and/or Si₃N₄. For most of these polymers pyrolysis and high temperature annealing in ammonia promotes the formation of the nitride at the expense of the oxide. Some of these ceramic precursor polymers will be considered as resins for the glass/ceramic insulation system.

The silicone resins (rubbers) are an attractive potential class of polymer precursors to silica if they are thermally degraded in air or oxygen rich atmospheres. By loading them with boron and /or other metal compounds the silicone resins are potential precursor polymers for silicate, borosilicate, and aluminosilicate glasses or glass ceramics.

Although there are a number of commercial manufacturers of silicone resins, a particularly attractive one is RTV 161, available from General Electric. This resin uses a non-corrosive alkoxy cure system, and decomposes in air above 300 °C. RTV 560 is another attractive pourable silicone resin that decomposes in air above 260 °C. Such resins have been demonstrated as precursors to SiC when thermally decomposed in ammonia.

A series of U.S. Patents have been issued to Myers⁴². They disclose silazane and silazane polymer precursors to SiC and Si₃N₄. When fired in air at 1500 °C the best of these precursor polymers gave char yields > 90% based on Si. Of course much of this residual silicon was present as silicon oxides or silicon oxycarbides.

Liquid, thermosetting Si-O-C-N pre-ceramic polymers also are disclosed. They could be very attractive resins for the glass/ceramic insulation system.

Myers also developed a silazane modified phenolic resin that gave an 80% char yield based on Si and C. This pre-ceramic polymer was developed as a matrix resin for the manufacture of C/C composite materials.

Resins that give high char yields of carbon during pyrolysis in inert atmospheres also are of interest as matrix resins for the glass/ceramic insulation, especially when loaded with metals or metal precursor powders. In these cases inert atmosphere pyrolysis would generate char residues rich in refractory metal compounds.

F. Cost comparison between SSC dipoles and block dipoles

It is absurd in general to argue *pro* or *con* the manufacturing cost of a superconducting magnet before one has built and tested model magnets and even pre-production prototypes. However, it is appropriate to address here one particular criticism which has been made on several occasions concerning the potential for cost savings in pressing magnet technology to the high-field frontier: "The cost of a high-field magnet is mainly in its superconductor. As one pushes field strength ever higher, the total quantity of superconductor for a given energy storage ring grows, hence the cost grows, so the magnet system cost will grow with field strength."

We have attempted to address this criticism by comparing the major cost elements which comprise an SSC dipole, whose costs are now well documented, to the analogous costs for a 16 Tesla block-coil dual dipole. The SSC dipole cost was evaluated thoroughly during the final DOE review of the project. Figure 4-31 shows the evolution of the estimate of the cost per 16.5 m dipole, as various cost-saving potentials were evaluated. The resulting cost per magnet was ~\$160,000, divided roughly equally between finished parts (superconductor, beam tube, cryostat components, collar laminations, etc.) and labor for assembly.

To compare the block-coil dipole design to that of the SSC $\cos \theta$ dipole, we must compare conductor costs, the cost of parts other than conductor, and the labor for assembly. In consultation with Dr. McInturff, who is familiar with all aspects of the SSC dipole fabrication and with the fabrication issues for Nb_3Sn coils, we have endeavored to make a rough comparison of the two designs:

Conductor. *NbTi/Cu cable* costs ~\$100/lb in production quantity. The total conductor cost for an SSC dipole is \$40,000 (\$2,530/m).

Nb₃Sn/Cu cable costs ~\$300/lb in small-quantity today. There has never been a production-quantity application; suppliers estimate a quantity cost in the range \$150-200/lb. The range of total conductor cost for a block-coil dual dipole would be \$29,000-39,000/m.

Magnet Parts. *SSC dipole:* Deducting the above conductor cost from the \$80,000 component cost for an SSC dipole, the cost of all other finished parts is ~\$40,000 (\$2,310/m).

Block-coil dipole: The number and size of finished parts (e.g. lamination pieces, beam tubes, He shells, end fittings for one block-coil dual dipole is roughly twice that for one SSC dipole.

Magnet labor. *SSC dipole:* The labor cost for all assembly processes (coil winding; beam tube assembly; coil assembly and ground plane installation; lamination stacking and welding; collar assembly, prestress, and welding; iron lamination stacking, welding, and assembly; outer shell assembly and welding) is ~\$80,000/magnet (\$4,840/m)

Block-coil dipole: The coil assemblies should be considerably simpler to build and position than those for a $\cos \theta$ dipole, but there are more of them. There is only one set of laminated collars, instead of the two sets (non-magnetic and magnetic) on a $\cos \theta$ dipole.

On the other hand the Nb₃Sn coil assembly must undergo a reaction bake. Unless our new concept for inorganic B-stage insulation is successful, it will have to be vacuum impregnated just like the cos θ dipoles. Overall we estimate that the labor for fabrication of one block-coil dual dipole is roughly twice that to fabricate one SSC dipole.

Table 3 presents a cost comparison of the overall cost of the dipole magnets for a $\sqrt{s} = 40$ TeV hadron collider, under the above assumptions. Two costs are estimated for the block-coil dipoles, corresponding to the low and high extremes of the conductor cost estimation. The range of costs for the block-coil case brackets that of the SSC dipoles: the magnet costs are likely to be comparable for given energy, given aperture, etc. For a 2.5-times higher field strength, the tunnel cost is proportionately cheaper, and the siting of an ultimate-energy collider is proportionately easier.

There is one additional, more subtle potential for further substantial cost savings. The block-coil design which is shown in Figure 4-4 and used in calculating the costs in Table 3 is designed to provide an aperture of 5 cm. As discussed above, both the physical aperture and the good-field aperture of the magnet are likely more than is required for an ultimate-energy, ultimate-field collider. The aperture of the SSC dipoles, which received a tremendous amount of attention during 1992, was increased to 5 cm primarily because the field quality and injection sextupole fields were marginal for collider requirements with the original 4 cm aperture. The field calculations to date indicate that both concerns may be in fact quite acceptable with a block-coil design. The quantity of superconductor in the block-coil design scales as the square of the aperture. Reducing from a 5 cm to a 4 cm bore would reduce superconductor cost by 36%, total magnet cost by 30%.

The original criticism regarding the cost of higher field is simply based upon a false assumption: the superconducting cable represents only ~25% of the cost of an SSC magnet. There is real potential for cost savings and project enhancement by pressing the high-field frontier. Whether the potential is real or not can only be found from the proposed R&D program.

MATERIAL COST MATRIX GRAPH AVERAGE RECURRING COST PER MAGNET

(CCB CHANGES ONLY)

Figure 4-37. Cost analysis of the SSC dipoles, from final DOE review.

Table 3. Cost comparison of SSC dipole and block-coil dipole

Cost element	SSC dipole	Block dual dipole		
cable conductor	NbTi/Cu	Nb3Sn/Cu		
cable cost	100	(low) 150	(high) 200	\$/m
central field	6.50	16	16	Tesla
amp-turns/beam	1	5	5	MA turns
superconductor cable area	1,440	11,000	11,000	mm ²
sc area/field strength/beam	222	344	344	mm ² /Tesla
magnet cable cost	2,530	29,040	38,720	\$/m
magnet components cost	2,310	4,620	4,620	\$/m
magnet labor cost	4,840	9,680	9,680	\$/m
total magnet cost	9,680	43,340	53,020	\$/m
total magnet length	126,720	25,740	25,740	m
total magnet ring cost	1,227	1,116	1,365	million \$

Research Plan

We have formed a collaboration with the Superconducting Magnet Program at Lawrence Berkeley Laboratory for the coordinated development of high field collider magnets which extend beyond the bounds imposed by NbTi superconductor and $\cos \theta$ coil geometry. It will be the only such effort in the world, so far as we are aware. The task is an ambitious one: it took 20 years to fully mature the conductor and magnet fabrication technologies for the current state-of-the-art. The task is manifestly a long-term R&D project. It is however absolutely vital if we are to prepare a credible technology base for possible future hadron colliders to push the energy frontier for high energy research.

We have developed a research plan for the first three years of the program, and an allocation of tasks between LBL and Texas A&M. The plan and milestones are summarized below, with detail provided in the WBS project schedule.

The design and fabrication of all prototype dipoles will be carried out at Texas A&M. We are requesting from TNRLC the allocation of the short-magnet fabrication facilities at SSCL. These facilities would give us an excellent basis for all aspects of magnet design and fabrication.

We have also requested from TNRLC and DOE the allocation of a short-magnet test cryostat, a liquid helium refrigerator system, and an ASSI magnet test electronics system which would support the testing of the dipoles at Texas A&M. Because of the necessity to plan our program with an absolute minimum of manpower, we plan to focus our hardware efforts during the first year entirely on commissioning the fabrication facilities and building the first two model magnets. LBL has agreed to test our first several magnets in their test cryostat. We plan to commission the refrigerator and the test electronics system during the second year, so that by the end of the second year we will be able to test magnets in-house.

LBL has agreed to supply us with all superconducting cable as required for our short model magnets. Their role in that respect is a tremendous boost, because they are among the most knowledgeable and best equipped group in the world for cabling and testing Nb₃Sn cable. LBL also plans to work with GE in developing and evaluating high-field Nb₃Sn tape, utilizing GE's tape process facility. If successful that effort would yield tape suitable for use in the pipe dipole PST-1 in the third year.

A summary list of the equipment which we are requesting from each of TNRLC and DOE follows the budget.

Year 1 Research Plan and Milestones

0. 13 Tesla $\cos \theta$ dipole tests (D20)

The D20 magnet should be completed in late 1993. Instrumentation for its testing is being built at the same time. Testing will commence in early 1994. One Texas A&M graduate student will come to LBL for ~6 months to participate in the testing (LBL support).

Milestone: Test results to be presented and reviewed at the Erice High-Field Magnet Workshop, May 1995.

1. NbTi block-coil dual dipole (BT-1)

The BT-1 magnet is a block-coil dual dipole, using NbTi cable. Its geometry, coil dimensions, and construction approach will be taken exactly from that of the 16 Tesla Nb₃Sn design. The purpose of BT-1 is to validate the field design, and to evaluate many practical issues of magnet fabrication: conductor placement tolerance, coil end strategy, preload strategy, and quench behavior. We may elect to use a B-stage epoxy insulation rather than vacuum impregnation, in order to evaluate some of the issues that will arise for the "inorganic B-stage" we plan to develop for use with Nb₃Sn coils. Because this magnet will be used for so many learning curves, it will be designed to be demountable so that we can try various coil, insulation, and preload approaches.

Milestone: Magnet tests in August 1995.

2. Insulation development

We plan to evaluate various options for a resin/glass/ceramic "B-stage" insulation scheme. Most tests will be conducted on small coil samples, to evaluate cure cycles, mechanical and electrical properties after reaction bake, and helium percolation. Once practical processes are developed, test coils will be built and tested in a steel flux shunt.

Milestone: Insulation development report to May 1995 review.

3. Nb₃Sn block-coil dual dipole (BS-1)

The BS-1 magnet will be our first prototype of the block-coil magnet with Nb₃Sn conductor. We will adapt the design and fabrication processes according to what we learn from BT-1. Issues of particular importance for this first model are evaluation of winding, reaction, insulation, and preload strategies. The coil will be instrumented with LBL strain gages throughout the coil assembly to measure the distribution of preload and Lorentz stress during cooldown, as a function of field strength, and during quench.

Milestone: Magnet testing in May 1996.

4. NbTi pipe magnet (PT-1)

PT-1 is another "learning magnet". We will use NbTi conductor in order to validate the field design, develop procedures for coil winding and assembly, and evaluate options for preload strategy. As with BT-1, all dimensions and design details will be taken directly from the Nb₃Sn design, so that we can evaluate the design and fabrication issues. Like BT-1, it will be designed to be demountable so that many tests can be made. One issue will perform be different, however: PT-1 will use NbTi cable, while the follow-on Nb₃Sn version may use tape conductor.

Milestone: Magnet testing in July 1996.

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
1	NbTi block-coil dual dipole																							
1.1	Magnetic design																							
1.1.1	Body coil design																							
1.1.2	Conductor placement errors																							
1.1.3	Persistent current multipoles																							
1.1.4	End coil design																							
1.1.5	Magnetic design review																							
1.2	Mechanical design																							
1.2.1	Body coil stress analysis																							
1.2.2	End coil stress analysis																							
1.2.3	Coil winding strategy																							
1.2.4	Coil insulation preliminary design																							
1.2.5	Non-magnetic core design																							
1.2.6	Preload strategy																							
1.2.7	Magnetic core design																							
1.2.7.1	Banding preload																							
1.2.7.2	Piston preload																							
1.2.7.3	Gap w/aluminum spacer preload																							
1.2.8	End coil support design																							
1.2.9	Stamping die designs																							
1.2.10	Mechanical design review																							
1.3	Electrical design																							
1.3.1	Quench simulations																							
1.3.2	Quench protection design																							
1.3.3	Charging circuit design																							
1.3.4	Electrical design review																							

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
1.4	Cryogenic design																							
1.4.1	Cold mass design																							
1.4.2	He circuit design																							
1.4.3	Cooldown strategy																							
1.4.4	Quench-mode vapor transport																							
1.4.5	Cryogenic design review																							
1.5	Fabrication development																							
1.5.1	NbTi cable																							
1.5.1.1	Conductor																							
1.5.1.2	Cabling and insulation																							
1.5.2	Coil winding prototypes																							
1.5.2.1	Winding fixtures																							
1.5.2.2	End supports																							
1.5.2.3	Winding																							
1.5.3	Test practice coils																							
1.5.4	Lamination structures																							
1.5.4.1	Laminations																							
1.5.4.2	Stacking fixture																							
1.6	Design review																							
1.7	Design revisions																							
1.8	Magnet fabrication																							
1.8.1	Lamination structures																							
1.8.1.1	Stack & weld blocks																							
1.8.1.2	Assemble cores																							
1.8.1.2.	Coil cores																							
1.8.1.2.	Steel cores																							

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

Critical Progress Summary
 Noncritical Milestone Rolled Up

Project:
 Date: 10/27/94

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
2.2.7	End coil support																							
2.2.8	Stamping die design																							
2.2.9	Mechanical design review																							
2.3	Coil insulation preliminary design																							
2.4	Electrical design																							
2.4.1	Quench simulations																							
2.4.2	Quench protection design																							
2.4.3	Charging circuit design																							
2.4.4	Electrical design review																							
2.5	Cryogenic design																							
2.5.1	Cold mass design																							
2.5.2	Heat transport in coil, lamination str																							
2.5.3	He circuit design																							
2.5.4	Cooldown strategy																							
2.5.5	Quench-mode vapor transport																							
2.5.6	Cryogenic design review																							
2.6	Fabrication development																							
2.6.1	Insulation development																							
2.6.1.1	Cable impregnation process de																							
2.6.1.2	Design insulation system																							
2.6.1.3	Measure mechanical, thermal,																							
2.6.1.4	Wind and react prototype coil																							
2.6.1.5	Test performance																							
2.6.1.6	Insulation design review																							
2.6.2	Nb3Sn cable																							
2.6.2.1	Conductor																							

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

WBS	Name	Qtr 4, 1994				Qtr 1, 1995				Qtr 2, 1995				Qtr 3, 1995				Qtr 4, 1995				Qtr 1, 1996				Qtr 2, 1996				Qtr 3, 1996								
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug		
2.6.2.2	Cabling																																					
2.6.2.3	Insulation																																					
2.6.3	Lamination structures																																					
2.6.3.1	Stamping die designs																																					
2.6.3.2	Laminations																																					
2.6.3.3	Stacking fixture																																					
2.6.4	Coil winding prototypes																																					
2.6.4.1	Winding fixtures																																					
2.6.4.2	End supports																																					
2.6.4.3	Reaction bake fixtures																																					
2.6.4.4	Practice coils																																					
2.6.4.4.	Winding																																					
2.6.4.4.	Reaction bake																																					
2.6.4.5	Test practice coils																																					
2.6.5	Review at Ericc Magnet Workshop																																					
2.6.6	Design revisions																																					
2.7	Magnet fabrication																																					
2.7.1	Lamination structures																																					
2.7.1.1	Stack & weld blocks																																					
2.7.1.2	Assemble cores																																					
2.7.1.2.	Coil cores																																					
2.7.1.2.	Steel cores																																					
2.7.1.3	End supports																																					
2.7.2	Coil winding																																					
2.7.2.1	Coil 1 (3 colls)																																					
2.7.2.2	Coil 2 (3 colls)																																					

Project: Date: 10/27/94	Critical	Progress	Summary
	Noncritical	Milestone	Rolled Up

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
2.7.3	Reaction bake																							
2.7.3.1	Coil 1																							
2.7.3.2	Coil 2																							
2.7.4	Install instrumentation																							
2.7.5	Cold mass assembly																							
2.6.8.7	Prestress cold mass																							
2.8	Assemble magnet in cryostat																							
2.9	Magnet testing																							
2.10	Performance review																							
3	Cryostat																							
3.1	Design/modifications																							
3.1.1	Vacuum vessel																							
3.1.2	Cold mass supports																							
3.1.3	77K shield																							
3.1.4	20K shield																							
3.1.5	He circuit																							
3.1.6	Current leads																							
3.2	Instrumentation																							
3.3	Fabrication																							
3.4	Testing																							
4	NbTi pipe dipole																							
4.1	Magnetic design																							
4.1.1	Dipole coil design																							
4.1.2	Toroid coil design																							
4.1.3	Conductor placement errors																							
4.1.4	Persistent current multipoles																							

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
4.4	Cryogenic design																							
4.4.1	Cold mass design																							
4.4.2	Heat transport in coll, lamination str																							
4.4.3	He circuit design																							
4.4.4	Cooldown strategy																							
4.4.5	Quench-mode vapor transport																							
4.5	Fabrication development																							
4.5.1	NbTi cable																							
4.5.1.1	Conductor																							
4.5.1.2	Cabling & insulation																							
4.5.3	Lamination structures																							
4.5.3.2	Laminations																							
4.5.2.1.	Non-magnetic cores																							
4.5.2.1.	Magnetic cores																							
4.5.2.1.	Interleaved collar																							
4.5.3.3	Stacking fixtures																							
4.5.3.4	Stack & weld blocks																							
4.5.3	Coil winding prototypes																							
4.5.3.1	Winding fixtures																							
4.5.3.2	End coil supports																							
4.5.3.3	Practice coils																							
4.5.3.3.	Dipole coll																							
4.5.3.3.	Toroid coll																							
4.5.3.4	Test practice coils																							
4.6	Design review																							
4.7	Design revisions																							

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
4.8	Magnet fabrication																							
4.8.1	Lamination structures																							
4.8.1.1	Stack & weld blocks																							
4.8.1.2	Assemble cores																							
4.8.1.2.	Coil cores																							
4.8.1.2.	Steel cores																							
4.8.2	Coil winding																							
4.8.2.1	Dipole coils																							
4.8.2.2	Toroid coils																							
4.8.3	Install instrumentation																							
4.8.4	Cold mass assembly																							
4.8.5	Prestress cold mass																							
4.9	Assemble magnet in cryostat																							
4.10	Magnet testing																							
4.11	Performance Review																							

Project: Date: 10/27/94	Critical		Progress		Summary	
	Noncritical		Milestone	◆	Rolled Up	◇

Personnel (Gigatron)

Principal Investigator.

Peter M. McIntyre is a Professor of Physics at Texas A&M University. He has been devising new technology for accelerators for 15 years, including $p\bar{p}$ colliding beams, beam cooling experiments, gas microstrip chambers, superferrie magnets for hadron colliders, and of course gigatron.

Physicists.

Jochen Trost is an Associate Research Scientist, who has been working on gigatron for the past three years.

Yaoqi Pang is a senior technologist with particular expertise in materials science and microfabrication techniques.

Students.

Bo Lee and **Don Smith** have both recently graduated after completing thesis research on the gigatron technologies.

Howard Demroff has experience with microwave techniques as well as clean-room fabrication technology.

Marcus Drew has built component elements of several of our fabrication instruments.

Technicians.

Tim Elliott is an electronic technician and also a CAD designer. He has wide expertise in the techniques and equipment we use to metalize and etch silicon.

Tapan Mazumdar is a technical physicist, with excellent hands-on ability to operate, tune, and repair our various elderly process fabrication equipment.

Personnel (High-Field Magnets)

The proposed project is an attempt to bring together a number of outstanding scientists, engineers, and technicians, half of whom are being laid off from the Super Collider, and a strong base of equipment from SSCL, to create a lean, mean team for design, building, and testing superconducting magnets. The team comprises all of the skills and experience necessary to assure an efficient, successful magnet R&D effort.

Principal Investigator.

Peter M. McIntyre is a Professor of Physics at Texas A&M University, and has a number of accelerator accomplishments to his credit: invention of $p\bar{p}$ colliding beams, beam cooling experiments at Fermilab, and development of the superferric design for collider magnets.

Physicists.

Sergio Pissanetzky is a Senior Scientist at the Houston Advanced Research Center. He has authored ~50 designs for advanced superconducting magnets, including the superferric collider magnets, a 4 Tesla whole-body MRI magnet, a high-current SMES test facility, and an open-geometry MRI magnet. Dr. Pissanetzky is author of MAGNUS, a 3-D Poisson code, and OPUS, a code which performs a constrained optimization of magnet design for multiple constraints and weighted performance criteria.

Charles Meitzler is a Professor of Physics at Sam Houston State University. He has ~15 years experience with linear accelerators and r.f. quadrupoles. During the past 5 years he has developed a state-of-the-art facility for precision measurement of high-field NMR spectroscopy magnets and of persistent-current joints for MR solenoids.

Gan Liang is a Professor of Physics at Sam Houston State University. He is a metallurgist, and has worked for the past 5 years on the development of improved techniques for insulating Nb₃Sn coils.

Weijun Shen is a pre-doctoral Research Assistant at Texas A&M University. He has conducted most of the calculations which are the basis of this proposal. He worked at SSCL for 2 years in magnet development, and built and tested several successful magnets there before joining Texas A&M two years ago.

Damir Latypov is a post-doctoral Research Associate at Texas A&M University. He has spent the past three years calculating quench propagation in a variety of magnets, and in making some of the most definitive measurements to date to experimentally validate quench simulations over a range of coil parameters.

Tarikh Jaffery has been a Scientist at SSCL. He has worked at both Fermilab and SSCL in testing the performance of the prototype magnets and the half-cell string at SSCL. He is familiar with all aspects of test design, hardware, and procedure.

Engineers.

John Colvin is a senior cryogenic engineer at the Houston Advanced Research Center. He has ~20 years experience at Fermilab and at HARC in design, operation, and debugging of all forms of cryogenic equipment: refrigerators, compressors, cryocoolers, complex cryostats.

Richard Sims is a senior design engineer at SSCL. He has broad experience in project management, and in design and operation of most of the equipment which would be used to fabricate and test short model magnets.

Robert Wendt is a mechanical designer and engineer who has designed and built a wide variety of magnet fabrication equipment and cryostats. He worked at Fermilab for 15 years before joining SSCL.

Lucien Plesia is an electrical engineer with four years experience in control systems and data acquisition. He is the most knowledgeable expert on the hardware and software of the ASST test system.

Technicians.

Andrew Jaisle is a senior accelerator technician, with 10 years of experience at Brookhaven and SSCL in all aspects of superconducting magnet fabrication.

Mike Hentjes is a senior accelerator technician, with 15 years of experience at Fermilab and SSCL in building superconducting magnets, operating refrigerators, and conducting magnet measurements.

Richard Applegate is an accelerator technician with 5 years experience in assembling, commissioning, and operating the ASST system.

Tim Elliott is both an electronic technician and a CAD draftsman of excellent ability. He is expert in a wide range of vacuum techniques and in electronic equipment operation and repair.

¹ H.M. Bizek *et al.*, IEEE Trans. Plasma Sci. **16**, p.258 (1988);

² H.M. Bizek *et al.*, IEEE Trans. Electron Devices **ED-36**, p.2720 (1989).

³ B. Lee *et al.*, "Knife-edge thin-film field emission cathodes", Proc. 1993 Particle Accelerator Conf., Washington, DC (1993).

⁴ D.D. Smith *et al.*, "The oxidized porous silicon field emission array", Proc. 1993 Particle Accelerator Conf., Washington, DC (1993).

⁵ C.A. Spindt *et al.*, J. Appl. Phys. **47**, p.7089 (1976).

⁶ C.A. Spindt *et al.*, "Field emission array development," Proc. 33rd Intl. Field Emission Symposium, Berlin, Germany, July 1986.

⁷ W.K. Yue, "Electron Field Emission in Porous Silicon," Dissertation, Department of Electrical Engineering, Texas A&M University, August 1991 (unpublished).

⁸ Bo Lee *et al.*, Appl. Surface Sci. **67**, p.66 (1993).

⁹ R.C. Jaklevic, L. Elie, W. Shen and J.T. Chen, Appl. Phys. Lett. **52**, p.1656 (1988).

R.C. Jaklevic *et al.*, J. Vac. Sci. Technol. **86**, p.448 (1988).

¹⁰ A. Uhlir, Bell System Technical Journal **35**, 333 (1956).

¹¹ V. Lehmann, J. Electrochem. Soc. **140**, 2836 (1993).

¹² T. Unagami, J. Electrochem. Soc. **127**, 476 (1980).

D.R. Turner, *Surface Chemistry of Metals and Semiconductors*, ed. H.C. Gatos, John Wiley & Sons, New York, 1960. pt III, p. 285.

Y. Arita, J. Crystal Growth **45**, 383 (1978).

¹³ R. Memming and G. Schwandt, Surface Sci. **13**, 265 (1969).

¹⁴ T. Unagami, J. Electrochem. Soc. **127**, 476 (1980).

¹⁵ R.C. Jaklevic *et al.*, J. Vac. Sci. Technol. **A6**, 448 (1988).

¹⁶ M.I.J. Beale *et al.*, J. Crystal Growth **73**, 622 (1985).

P. Searson *et al.*, J. Appl. Phys. **72**, (1993).

Peter M. McIntyre

DATE OF BIRTH: September 26, 1947
EDUCATION: B.A. degree, Physics, University of Chicago, 1967
M.S. degree, Physics, University of Chicago, 1968
Ph.D. degree, Physics, University of Chicago, 1973

POSITIONS HELD:

1968--1969: Instructor, University of Chicago.
1972--1974: Research Associate, Enrico Fermi Institute.
1974--1975: Visiting Scientist, CERN.
1975--1979: Assistant Professor, Harvard University.
1979--1980: Group Leader, Internal Target Group, Fermilab.
1980--1986: Associate Professor, Texas A & M University.
1984--1991: Spokesman, Texas Accelerator Center.
1993--1994: Director, Texas Accelerator Center
1986--present: Professor, Texas A&M University.
1988--present: President, Accelerator Technology Corporation.
1990--1991: President, The American Physical Society, Texas Section.
1990--1991: Associate Dean, College of Science, Texas A&M University.
1990--1993: President, Board of Trustees, St. Michael's Academy,

AWARDS AND FELLOWSHIPS:

Sloan Foundation Fellow, 1980--82.
IR-100 Award, 1981: electron beam development and electron cooling experiment
Governor's Citation of Merit, 1989, leadership in the Texas siting of the SSC.

PATENTS:

CUTS: continuous unitized tunneling system.
Gigatron: a high efficiency microwave power source for linac colliders.
Structured coil design for superconducting magnets.
Pipe Magnet: compact dual dipole for hadron colliders.

Peter Mastin McIntyre

Peter Mastin McIntyre is a Professor of Physics at Texas A&M University. He studied at the University of Chicago, where he received his Ph.D. in 1973. He performed experiments with colliding beams at CERN in Geneva, Switzerland until 1975, then joined Harvard University as Assistant Professor. While there, he participated in neutrino scattering experiments at Fermilab. In 1976 he was the first to propose to make colliding beams of protons and antiprotons using the large synchrotrons at Fermilab and at CERN. This work led to the discovery of the weak bosons at CERN in 1982. He developed several techniques for cooling intense beams of antiprotons. In 1980 he was awarded an IR100 award for the invention of a new technique for high-efficiency collection of intense electron beams.

Since joining Texas A&M in 1980, he has conducted a search for magnetic monopoles in a nearby salt mine, and has participated in the construction and operation of the Collider Detector at Fermilab (CDF). Dr. McIntyre is an A.P.Sloan Foundation fellow, and is listed in *Who's Who in Science and Engineering*. Dr. McIntyre was among the first to propose the construction of the Superconducting Super Collider and was a co-author of the Texas SSC site proposal. In 1984, together with F.R. Huson, he founded the Texas Accelerator Center, a university-based laboratory for advanced accelerator research, and served as its Director in 1993-94. He has led the development of the relational database and curriculum development environment software for Project 2061, a national program for reform of K-12 science education. He is developing educational software for high energy physics and accelerator physics.

Dr. McIntyre is currently involved in three areas of research. He is participating in the CDF experiment at Fermilab, which is studying 2 TeV proton-antiproton collisions and has recently announced evidence for the top quark. He is developing new technology for future high-energy colliders: gigatron, a new high-power microwave amplifier for future e^+e^- linac colliders; a 16 Tesla dual dipole for future hadron colliders; and targetry and cooling for a 1 TeV $\mu^+\mu^-$ collider. He is developing the gas microstrip chamber, a new precision track chamber which offers excellent performance for high-energy collider experiments and also as an electronic X-ray camera for mammography.

Peter M. McIntyre

Publications

143. W boson + jet angular distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **73**, 2296 (1994).
142. Supersymmetry at a proposed $\sqrt{s} = 4$ TeV upgrade of the Fermilab Tevatron. (with T. Kamon, J.L. Lopez, and J.T. White), Phys. Rev. Lett. **50**, 5676 (1994).
143. Evidence for top quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D50**, 2966 (1994).
142. Evidence for top quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **73**, p. 225 (1994).
141. Measurement of the ratio $\sigma B(W \rightarrow \nu \bar{\nu}) / \sigma B(Z^0 \rightarrow e^+ e^-)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV (with F. Abe *et al.*), Phys. Rev. Lett. **73**, p. 220 (1994).
140. Measurement of the B^+ and B^0 meson lifetimes. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3456 (1994).
139. Measurement of the charged multiplicity of $Z^0 \rightarrow b \bar{b}$ events. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3145 (1994).
138. Search for excited quarks in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3004 (1994).
137. Search for the top quark decaying to a charged Higgs boson in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.1977 (1994).
136. Measurement of Drell-Yan electron and muon pair differential cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D49**, R1 (1994).
135. Search for first-generation leptoquarks in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV at CDF. (with F. Abe *et al.*), Phys. Rev. **D48**, p.R3939 (1993).
134. Prompt photon cross section measurement in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev **D48**, p. 2998 (1993).
133. Measurement of the dijet mass distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D 48**, p.998 (1993).

132. Study of porous silicon morphologies for electron transport. (with Y. Pang *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2711.
131. The oxidized porous silicon field emission array. (with D.D. Smith *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2708.
130. Knife-edge thin film field emission cathodes. (with B. Lee *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2705.
129. Recent developments on gas microstrip chambers at Texas A&M. (with E.F. Barasch *et al.*), Proceedings of the 7th Meeting of the Am. Phys. Soc. Div. of Particles and Fields, 10-14 November 1992, Fermi National Accelerator Laboratory, Batavia, Illinois, vol.2, p.1782.
128. Gas microstrip detectors on polymer, silicon, and glass substrates. (with E.F. Barasch *et al.*), Nucl. Phys. B 32, p.216 (1993).
127. Development of knife-edge field emission cathodes on (110) silicon wafers. (with Bo Lee *et al.*), Appl. Surface Sci. 67, p.66 (1993).
126. Measurement of the average lifetime of B hadrons produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.3421 (1993).
125. Search for quark compositeness, axigluons and heavy particles using the dijet invariant mass spectrum observed in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.2542 (1993).
124. Inclusive χ_c and b-quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.2537 (1993).
123. Measurement of the bottom quark production in 1.8 TeV proton-antiproton collisions using muons from b-quark decays. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.2396 (1993).
122. Observation of $B_s^0 \rightarrow J/\psi \phi$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.1685 (1993).
121. Center-of-mass angular distribution of prompt photons produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.679 (1993).
120. Measurement of the bottom-quark production cross section using semileptonic decay electrons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. 71, p.500 (1993).

119. Study of four-jet events and evidence for double parton interactions in pp collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **47**, p.4857 (1993).
118. Measurement of the cross section for production of two isolated prompt photons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2232 (1993).
117. Measurement of jet multiplicity in W events produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.4042 (1993).
116. First measurement of the left-right cross-section asymmetry in Z boson production by pp collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2515 (1993).
115. Measurement of the cross section for production of two isolated prompt photons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2232 (1993).
114. Search for $\Lambda_b \rightarrow J/\psi \Lambda$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **47**, p.R2639 (1993).
113. Comparison of jet production in $\bar{p}p$ collisions at $\sqrt{s} = 546$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.1376 (1993).
112. Measurement of jet shapes in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.713 (1993).
111. The pipe magnet: compact 13 Tesla dual dipole for future hadron colliders. (with E. Badea and S. Pissanetzky), Proc. HEACC'92 Conference, Hamburg, Germany (1992).
110. Limits on the production of massive stable charged particles. (with F. Abe *et al.*), Phys. Rev. D **46**, R1889 (1992).
109. Inclusive $J/\psi(2S)$ and b-quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.3704 (1992).
108. Dijet angular distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.2896 (1992).
107. Limit on the rare decay $W \rightarrow \gamma\pi$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.2160 (1992).

106. RF breakdown and field emission measurement of SiO₂-coated copper electrodes. (with D. Sun *et al.*) Proc. 1992 Linear Accelerator Conf., August 24-28, 1992, Ottawa, Ontario, Canada, ed. C.R. Hoffmann, AECL-10782, vol. 2, p.
105. Gated field-emitter cathodes for high-power microwave applications. (with E. Barasch *et al.*), Proc. 1992 Linear Accelerator Conf., August 24-28, 1992, Ottawa, Ontario, Canada, ed. C.R. Hoffmann, AECL-10782, vol. 2, p. 519.
104. Measurement of the production and muonic decay of W and Z bosons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p. 28 (1992).
103. Measurement of the B-meson and b-quark cross sections at $\sqrt{s} = 1.8$ TeV using the exclusive decay $B \rightarrow J/\psi K$. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 3403 (1992).
102. Measurement of the ratio $B(W \rightarrow \tau \nu) / B(W \rightarrow e \nu)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 3398 (1992).
101. Limit on the top-quark mass from proton-antiproton collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 3921 (1992).
100. Measurement of the isolated prompt photon cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 2734 (1992).
99. Gas microstrip chambers. (with E.F. Barasch *et al.*), Nucl. Instr. and Meth. in Phys. Res., **A315**, p. 170 (1992).
98. Properties of events with large total transverse energy produced in proton-antiproton collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 2249 (1992).
97. Search for new gauge bosons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1463 (1992).
96. Lepton asymmetry in W boson decays from $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1458 (1992).
95. Topology of three-jet events in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 1448 (1992).
94. Inclusive jet cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1104 (1992).

93. Lower limit on the top-quark mass from events with two leptons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p.447 (1992).
92. Measurement of $B^0 - \bar{B}^0$ mixing at the Fermilab Tevatron Collider. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.3351 (1991).
91. Measurement of the QCD jet broadening in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **44**, p.601 (1991).
90. Measurement of the Z boson p_t distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2937 (1991).
89. Search for $W \rightarrow e\nu$ and $W \rightarrow \mu\nu$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2609 (1991).
88. Measurement of the e^+e^- invariant-mass distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2418 (1991).
87. Measurement of $\sigma_B(W \rightarrow e\nu)$ and $\sigma_B(Z \rightarrow e^+e^-)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **44**, p.29 (1991).
86. Gated field-emission cathodes for microwave devices. (with H.P. Demroff *et al.*), Proc. IEEE Part. Acc. Conf., San Francisco, May 1991.
85. Measurement of the W boson p_t distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **66**, p.2951 (1991).
84. The microstrip chamber: ultraprecise tracking for SSC detectors. (with E.F. Barasch *et al.*), Proc. Symp. on Detector Research and Development for the SSC, Fort Worth, Texas, p.209 (1990).
83. Measurement of the W boson mass. (with F. Abe *et al.*), Phys. Rev. Lett. **65**, p.2243 (1990).
82. Jet-fragmentation properties in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **65**, p.68 (1990).
81. Two-jet invariant-mass distribution at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **41**, p.1722 (1990).
80. Search for a light Higgs boson at the Fermilab Tevatron proton-antiproton collider. (with F. Abe *et al.*), Phys. Rev. D **41**, p.717 (1990).

79. Measurement of D^* production in jets from pp Collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.48 (1990).
78. Measurement of the ratio $W \rightarrow e\nu / Z \rightarrow ee$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.152 (1990).
77. Search for new heavy quarks in electron-muon events at the Fermilab Collider. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.147 (1990).
76. Pseudorapidity distributions of charged particles produced in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. D **41**, 2330 (1990).
75. Two-jet differential cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.57 (1990).
74. Search for the top quark in the reaction $\bar{p}p \rightarrow \text{electron} + \text{jets}$ at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.142 (1990).
73. K_S^0 production in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. D **40**, p.3791 (1989).
72. Gigatron. (with H. Bizek *et al.*), IEEE Trans. on Electron Dev. **36**, p.2720 (1989).
71. Search for heavy stable charged particles in 1.8 TeV $\bar{p}p$ collisions at the Fermilab collider. (with F. Abe *et al.*), Phys. Rev. Lett. **63**, p.447 (1989).
- 70. The high field superferric magnet II. (with J.C. Colvin *et al.*), Particle Accelerators **30**, p.691 (1990).
69. Recent developments of gigatron technology. (with S.M. Elliott *et al.*), Particle Accelerators **30**, p.169 (1990).
68. Measurement of the mass and width of the Z^0 boson at the Fermilab Tevatron. (with F. Abe *et al.*), Phys. Rev. Lett. **63**, p.720 (1989).
67. Dijet angular distributions from $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.3020 (1989).
66. Limits on the masses of supersymmetric particles from 1.8 TeV $\bar{p}p$ collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.1825 (1989).
65. Advanced forward calorimetry for the SSC and Tevatron Collider.. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A279**, p.100 (1989).

64. Measurement of W boson production in 1.8 TeV $\bar{p}p$ collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.1005 (1989).
63. Laboratory detector for solar axions. (with K. van Bibber, D.E. Morris, G.G. Raffelt), Phys. Rev. D **39**, p. (1989).
62. Measurement of the inclusive jet cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.613 (1989).
61. Neutron-induced pulses in CDF forward hadron calorimeter. (with S. Cihangir *et al.*), IEEE Nucl. Sci. Symp. Orlando, Florida (1988).
60. Gigatron: a new technology for microwave power devices. (with S.M. Elliott *et al.*), Proc. SPIE Symp. on High Power Microwave Devices, Los Angeles (1988).
59. Gigatron. (with H.M. Bizek *et al.*), Proc. Workshop on Physics of Linear Colliders, Capri, Italy, p.377 (1988).
58. Transverse momentum distributions of charged particles produced in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. Lett. **61**, p.819 (1988).
57. A microwave power driver for linac colliders, Gigatron. (with H.M. Bizek *et al.*), Proc. Summer Study on High Energy Physics in the 1990's, Snowmass, CO, p.660 (1988).
56. The high-field superferric magnet. (with J.C. Colvin *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A270**, p.207 (1988).
55. Gigatron. (with H. Bizek, D. Raparia, and C. Swenson), IEEE Trans. Plasma Sci. **16**, p.58 (1988).
54. The CDF forward/backward hadron calorimeter. (with S. Cihangir *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A267**, p.249 (1987).
53. The ribbon lasertron. (with D. Raparia and C. Swenson), Proc. 1987 IEEE Particle Accel. Conf., p.1688 (1987).
52. Multi-MeV accelerator system for ion implantation. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **B24/25**, p.83 (1987).
51. Multi-MeV ion implantation accelerator system. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **B21**, p.55 (1987).

50. Search for super-heavy GUT magnetic monopoles in cosmic rays. (with C. Gagliardi *et al.*), Phys. Rev. D **35**, p.917 (1987).
49. The Collider Detector at Fermilab. (CDF) (with F. Abe *et al.*), IEEE Trans. Nucl. Sci. NS **33**, p.40. (1986).
48. A filter technique for shower shape discrimination, Forward Collider Physics Workshop. Fermilab, August 10, 1985.
47. The Texas Accelerator Center and the SSC, Proc. European Phys. Soc.; Bari, Italy. p.614, July, 1985.
46. Superferric magnet option for the SSC. (with H. Bingham *et al.*), IEEE Trans. Nucl. Sci. NS **32**, p.3462 (1985)
45. The three ring circus. (with D. Neuffer, W. Schmidt), IEEE Trans. Nucl. Sci. NS **32**, p.1704 (1985)
44. Superconducting Super Accelerator - challenge and opportunity. Proc. SSC Fixed Target Workshop, The Woodlands, Texas, January 26-30, p.1 (1984).
43. How to expose t quarks hidden in $\bar{p}p$ Collisions. (with M. Dechantsreiter, F. Halzen and D.M. Scott), Phys. Rev. D **25**, p.258 (1982).
42. Searching for the GUT monopole, Proc. 1982 Workshop on Proton Decay Experiments, Argonne National Laboratory. ANL-HEP-PR-82-24, p.352 (1982).
41. Electron cooling for the Fermilab antiproton source. (with W. Kells, F. Krienen, F.E. Mills, L. Olekiuk and J. Peoples), IEEE Trans. Nucl. Sci. NS **28**, p.2583 (1981).
40. Electron cooling experiments at Fermilab. (with R. Forster *et al.*), IEEE Trans. Nucl. Sci. NS **28**, p.2386 (1981).
39. Nucleon structure functions from measurement of inelastic neutrino and antineutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. D **23**, p.1045 (1981).
38. The forward spectrometer of the Fermilab Colliding Detector Facility, Proc. Madison Conf. on pp Collider Physics. AIP Conf. Proc. #85, p.263 (1981).
37. Very high energy antiproton physics: colliding 1 TeV "antiquarks" on heavy nuclei. (with F. Halzen), Phys. Rev. D **21**, p.726 (1980).
36. The Fermilab High-Intensity Antiproton Source. Design Report. Fermilab (1979).

35. A filter technique for stochastic cooling of betatron oscillations. Fermilab TM-920 (1979).
34. The $\bar{p}p$ Program at Fermilab. Proc. XIVth Rencontre de Morionde, (Editions Frontiers, Paris) (1979).
33. Electron beam diagnostics in the Fermilab electron cooling experiment. (with W.P. Kells), IEEE Trans. Nucl. Sci. NS 26, p.3300.
32. The electron beam for the Fermilab electron cooling experiment (with W.B. Herrmannsfeldt *et al.*), IEEE Trans. Nucl. Sci. NS 26, p.3237.
31. Initial operation of the Fermilab antiproton cooling ring. (with D.B. Cline *et al.*), IEEE Trans. Nucl. Sci. NS 26, p.3158 (1979).
30. Measurement of the structure functions in neutrino and antineutrino inelastic interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, p.1317 (1979).
29. Rates and properties of trimuon events observed in high energy neutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, 1024 (1979).
28. Fast event recorder utilizing a CCD analog shift register. (with R.J. Ducar), Proc. 1978 IEEE Nucl. Sci. Symp., Washington, D.C., (1978).
27. Very high luminosity proton-antiproton storage rings. (with D.B. Cline, F.E. Mills and C. Rubbia), submitted to Phys. Rev. Lett., October, 1978.
26. Measurement of the energy and x dependence of the y distributions in antineutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, p.149 (1979).
25. Fermilab Electron Cooling Experiment Design Report. (with J. Bridges *et al.*) Fermilab (1978).
24. Rates and properties of opposite-sign dimuons from neutrinos and antineutrinos. (with A. Benvenuti *et al.*) Phys. Rev. Lett. 41, p.204 (1978).
23. Evidence for the production of prompt like-sign dimuon events by high-energy neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 41, p.725 (1978).
22. ARGONAUT -- A novel detector for very high energy neutrino interactions. (with G. Harigel, H. Kautzky, and A. VanGinneken), Fermilab Proposal No.601D (1978).
21. Accommodating stochastic cooling at Fermilab. (with A. Ruggiero), Proc. Workshop on Producing High Luminosity, High Energy Proton-Antiproton Collisions, Lawrence Berkeley Laboratory (1978).

20. Further observation of trimuon production by neutrinos and antineutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **40**, p.8, p.488 (1978).
19. Limits of the probability that trimuons are produced by a new short-lived source of neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **40**, p.432 (1978).
18. Measurements of the proton-proton total cross-section and small-angle elastic scattering at ISR energies. (with L. Baksay *et al.*), Nucl. Phys. **B141**, p.1 (1978).
17. Characteristics of neutrino-produced dimuon and trimuon events as evidence for new physics at the lepton vertex. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **38**, p.1183 (1977).
16. Observation of a new process with trimuon production by high-energy neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **38**, p.1110 (1977).
15. Phase space cooling and $\bar{p}p$ colliding beams at Fermilab. (with E.R. Gray *et al.*), Proc. 1977 Part. Accel. Conf., p.1854 (1977).
14. Antiproton decay and the baryon number of the universe. (with D.B. Cline and C. Rubbia), Phys. Lett. **66B**, p.429 (1977).
13. How to observe the weak bosons in proton-antiproton collisions using existing accelerators. (with C. Rubbia and D. Cline), Proc. Int. Neutrino Conf., Aachen (Vieweg, Braunschweig), p.683 (1976).
12. Collecting antiprotons in the Fermilab Booster and very high energy $\bar{p}p$ interactions. (with D.B. Cline, F.E. Mills, C. Rubbia). Fermilab TM-689 (1976).
11. A new measurement of the K_S lifetime. (with S.H. Aronson *et al.*), Nuovo Cimento **32A**, p.236 (1976).
10. Evidence for double pomeron exchange at the CERN ISR. (with L. Baksay *et al.*), Phys. Lett. **61B**, p.89 (1976).
9. Experimental observation of copious yield of electrons with small transverse momenta in pp collisions at high energies. (with L. Baum, M.M. Block, B. Couchman, J. Crawford, A. Derevshchikov, D. DiBitonto, I. Golutvin, H. Hilscher, J. Ilion, A. Kernan, V. Kukhtin, J. Layter, W. Marsh, D. Schinzel, B. Shen, A. Staude, G. Tarnopolsky, R. Voss), Phys. Lett. **60B**, p.485 (1976).
8. Search for long-lived penetrating neutral particles. (with A. Benvenuti, D.B. Cline, W.T. Ford, R. Imlay, R.B. Jensen, T.Y. Ling, A.K. Mann, R. Orr, D.D. Reeder, J.

Rich, C. Rubbia, R. Stefanski, L. Sulak, P. Wanderer), Phys. Rev. Lett. **35**, p.1486 (1975).

7. Precision experiments on muonium III: Ramsey resonance in zero field. (with D. Favart, D.Y. Stowell, V.L. Telegdi, R. DeVoe, and R. Swanson), Phys. Rev. **A8**, p.1195 (1973).
6. A new precision measurement of the muonium hyperfine interval in argon. (with H.E.G. Kobrak, M. Eckhause, D. Favart, W.P. Kells, A. Magnon, J. Roehrig, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Phys. Lett. **B 43**, p.526 (1973).
5. Muonium HFS splitting as a source of α . (with D. Favart, D.Y. Stowell, R.A. Swanson, V.L. Telegdi, and R. DeVoe). Proc. IVth Int. Conf. on Atomic Masses and Fundamental Constants, Teddington, England, September 6-10, 1971.
4. Quadratic hfs pressure shifts of muonium in argon and krypton. (with D. Favart, D.Y. Stowell, V.L. Telegdi, R. DeVoe, and R.A. Swanson), Phys. Rev. Lett. **27**, p.1340 (1971).
3. Precision measurement of the hyperfine interval of muonium by a novel technique: Ramsey resonance in zero field. (with D. Favart, D.Y. Stowell, R. DeVoe and V.L. Telegdi), Phys. Rev. Lett. **27**, p.1336 (1971).
2. Measurement of the muon magnetic moment by "double resonance" in muonium, and a new value of α . (with R. DeVoe, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Proc. Int. Conf. on Precision Measurement and Fundamental Constants, Gaithersburg, MD, Aug. 3-7, (1970).
1. Measurement of the muonium hfs splitting and of the muon moment by "double resonance", and a new value of α . (with R. DeVoe, A. Magnon, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Phys. Rev. Lett. **25**, p.1779 (1970).

DOE/ER/40904--T1

Abstract

This proposal requests funding for a 3-year renewal of the DOE advanced accelerator R&D (AARD) program at Texas A&M University. Our program to date has focused on the development of the gigatron, a compact high-efficiency microwave driver for future linac colliders. We report results and progress in that project, and plan to bring it to a milestone and conclusion by mid-1995. We propose to initiate a second project, the development of a new technology for ultra-high field superconducting magnets for future hadron colliders. This project builds upon two magnet designs which we have introduced during the past year, which have the potential for a dramatic extension of the achievable field strength for both dipoles and quadrupoles.

During the past year, we have achieved direct emission into vacuum from two gated field-emission cathode technologies, a knife-edge array and a porous silicon structure. Each cathode structure is designed to optimize direct microwave modulation. The gate geometry and drive conductor patterns for this purpose require multi-mask IC fabrication strategies, and have required substantial process development. Cathodes suitable for triode emission studies have been fabricated successfully. While these proof-of-principle tests are encouraging, considerable effort remains before either cathode could be incorporated within a microwave power device. At the same time, more conventional approaches to high power and high efficiency at C band have been improved to provide r.f. drive performance close to that required for the Next Linear Collider (NLC).

We propose to continue the present effort through the first six months of the extended program. The specific objective is to build and test a round-beam microwave-modulated cathode, which could either serve as a precursor to further development of microwave power devices or as a stand-alone modulated cathode for linacs. We intend to continue gigatron development toward those objectives, and will seek funding from other sources.

We propose to make a major shift in the direction of our AARD program: the development of ultra-high field superconducting magnets for future hadron colliders. During the past year we have invented field designs which promise to extend dipole field strength to 16 Tesla and quadrupole gradient to 300 T/m. We have devised coil fabrication techniques for Nb₃Sn coils which should provide simpler and more reliable fabrication and superior mechanical and thermal performance. One of the magnet designs, the pipe dipole, has a field geometry suitable for use with tape conductor, without the usual limitations due to charging currents, which ultimately could provide a basis for developing practical magnets with A15 or BSCCO conductors. We have formed a collaboration with the Superconducting Magnet Group at LBL, to develop and test magnets embodying these developments. The primary focus of the TAMU program will be dipoles; after the testing of the D20 dipole the primary focus of the LBL program will be quadrupoles. If successful, we would provide a twofold improvement in the state of the art of superconducting magnet technology for future hadron colliders.

A substantial base of equipment is requested from both DOE and the Texas National Research Laboratory Commission (TNRLC), from the inventory of assets which are to be transferred in the termination of the SSC. The equipment would be used to establish facilities for fabrication and testing of model magnets at Texas A&M University. In addition, interim salary support is requested from TNRLC and SSCL to bridge 9 SSC personnel during the transition period from their currently scheduled lay-off through the first months of the proposed grant renewal.

In support of the expanded scope of the program, TEES commits cost-sharing in the form of returned indirect costs, totaling \$800,000 during the 3-year period. A 20,000 sq.ft. facility has been allocated to house the magnet development activity.

The 3-year renewal proposal is structured in two tasks: fabrication and testing of a microwave cathode as a 6-month conclusion of the gigatron project; and high-field superconducting dipole development. For each task a scope of work, a schedule, and a budget are presented. The personnel for the program comprise the present group at Texas A&M University, collaborators at Sam Houston State University, and personnel who would relocate to Texas A&M from SSC and from HARC. The equipment and facilities required for the gigatron conclusion are all in place. The facilities for the dipole development project are available in a 20,000 sq.ft. allocation within a newly acquired building complex at Texas A&M University. A division of effort between the LBL group and the Texas A&M group has been negotiated, which uses to best advantage the expertise and facilities at each institution. The cost of facility improvements and moving and commissioning of the SSC equipment is contained within the cost-sharing accorded to the project by TEES. The objective of the proposed magnet program is to design, build, and test two short model magnets per year throughout the three-year period, thereby providing a meaningful empirical basis for the development a new generation of superconducting collider magnets.

DOE/ER/40904-T1

1. Gigatron Program

The first endeavor of our program has been the development of a compact, high-efficiency microwave power source for e^+e^- linac colliders. The luminosity of a linac collider will ultimately be limited by the energy efficiency with which the tremendous amount of microwave power (~ 100 MW/m) can be generated. For this purpose we invented and have been developing the gigatron, a new approach to microwave power tube design^{1,2}.

Gigatron as a microwave power technology.

The gigatron design concept is illustrated in Figure 1-1 and is described in detail in Appendix A. It features three novel developments: First, a gated field-emitter array is employed for the cathode, to produce a microwave-modulated electron beam directly into the vacuum. Second, rather than the conventional round beam, a ribbon beam geometry is adopted to mitigate limitations from space charge. Third, a traveling wave coupler is used to obtain optimum output coupling even with a wide ribbon beam. By contrast, all conventional microwave power tubes begin with a d.c. electron beam, accelerate it, modulate its energy, pass it through a drift region in which it develops a current modulation, then passes it through an output coupler. The modulation/drift section typically sets fundamental limits to the efficiency, power, and bandwidth of power tube technologies. By starting with a modulated beam, gigatron would be able to eliminate these stages altogether. The calculated performance of gigatron would considerably exceed anything yet achieved, and would meet the drive power requirements of linear collider designs²:

- 18 GHz operating frequency;
- 100 MW peak power for a 1 m device;
- 200 kV HV modulation;
- >50% efficiency;
- >40 dB power gain.

Cathode technology development.

Our work to date has focused on the modulated cathode which is the heart of the gigatron concept. We have achieved gated field emission and modulation of emitted beam into vacuum with each of two technologies: a knife-edge emitter array³ with ~ 200 Å edge radius, 1,000 Å gate spacing, and 8 μ m substrate spacing (Figure 1-2); and a porous silicon cathode⁴ with a dense pattern of field-emitting pores and a thin gold gate layer (Figure 1-3). During the past year this work has resulted in the thesis research and completion of degrees by two of our graduate students: Bo Lee (knife-edge arrays) and Don Smith (porous silicon). The copies of both students' theses are attached and provide a detailed report of our research to date.

Program milestones.

We began the gigatron development program in 1988 with a systematic conceptual design of the modulated cathode, ribbon beam geometry, and output coupler. The first great challenge in the development of the gigatron is the demonstration of a viable technology for using gated field emitters under microwave modulation. We extrapolated the possible performance from the then-available field emitter cathodes which had been successfully developed by C.A. Spindt *et al.*^{5,6} for

display applications. While these cathodes achieved high current density (up to 1000 A/cm^2), the drive power required for microwave modulation would severely compromise the power gain and average power which could be achieved in a gigatron. We addressed this problem by developing a design for a resonant input coupler, shown in Figure 1-4. The coupler localizes the current flow which is required to charge and discharge the gate/cathode junction, and thereby improves modulation performance by 20 dB.

In 1990, our tests of tip-array field emission cathodes fabricated by Spindt et al.^{5,6} at SRI enabled us to identify specific features of the cathode structure which limit microwave modulation. These include resistivity of the gate film and substrate, parasitic capacitance between gate and substrate, susceptibility of the gate to damage during high-voltage breakdown, and insufficient dielectric strength on the gate/substrate insulation to support the bias voltage needed to sustain large emission current density. In 1991, we set out to develop two new kinds of highly emissive field emission cathodes: a stripline knife-edge cathode which increases the surface density of emitters by a factor of 100 compared to tip arrays, and a porous silicon cathode, inspired by studies of diodes that had been conducted at the TAMU Dept. of Electrical Engineering⁷.

Our original knife-edge cathode design was improved in 1992 with a new fabrication approach⁸ which produces very sharp, tall blades and a very narrow control gap for modulation, as shown in Figure 1-2. In the summer of 1993, we succeeded in generating field emission into vacuum from the improved knife-edge array, with a turn-on voltage for emission of about 25 V. Our work to date in developing the knife-edge cathodes is presented in the thesis of Bo Lee (Appendix C). While we have succeeded in obtaining gated emission from the new cathodes, we are still struggling with the control of one fabrication process step, which frequently leaves a shard of gold in the crucial control gap, causing shorting of the gate and arc damage to the diode region. This remaining problem should be viewed in a context of complete success in achieving excellent process control over all other process steps, each of which in its turn posed a similarly serious obstacle. We are currently adapting an electroless plating process, developed at IBM, which produces the gate metalization and its gate opening at the knife-edge without the plasma etching step which gives the troublesome shard. This is the last step of the process, and we should then be able to routinely fabricate successful cathodes.

We obtained a very early preliminary success in diode emission from porous silicon layers: 1 mm^2 cathodes delivered 20 A/cm^2 peak current for a gate modulation voltage of only 10 V. After a considerable effort of varying and tuning the manufacturing process parameters, we produced field emission from porous silicon in a triode configuration, directly into vacuum, near the end of 1992 - to our knowledge the first time this has ever been observed. Since then, new record emissivity has been achieved with porous silicon emitters in diode tests (now in vacuum), with a current density of 700 A/cm^2 at 18.6 V modulation in pulsed mode (1.4 A from an area of about 0.2 mm^2). We have developed a triode cathode in which the emission into vacuum is controlled by a thin ($\sim 50 \text{ \AA}$ thick) gold metalization, in a configuration which accommodates low charging impedance and small parasitic capacitance. Our work to date in developing the oxidized porous silicon (OPS) cathodes is presented in Appendix B (Mr. Smith's thesis). We have succeeded in fabricating and testing such cathodes (Figure 1-3). Figure 1-5 shows the first-ever observation of modulated direct emission into vacuum from a gated porous silicon triode.

The fabrication of both cathode devices has required a steadily growing sophistication in process technology. During the past three years, we have commissioned two class 100 clean rooms, a lithography system, a magnetron sputtering system, an oxidation furnace, a mask aligner, two etchers, a wire bonder, a wafer saw, a vacuum test stand, a laser-backscatter end-point detector, and a cryogenic evaporator⁹.

For each cathode technology we have succeeded in controlling the geometry, materials, and surfaces of devices with a feature size of $\sim 1,000$ Å. We have built and tested triode prototypes of each technology. The current density required for the gigatron cathode has been achieved in diode operation, and the cathode gate structure should support a bandwidth up to 30 GHz. Unfortunately however, neither technology is yet capable of producing robust cathodes. Our results to date demonstrate that the goal of 12 GHz emission, 20 A/cm^2 current density is achievable. The required current density has not yet been achieved in triode prototypes, although substantial progress has been made. At the same time, more conventional approaches to high power and high efficiency at C band have improved to provide performance close to that required for the Next Linear Collider (NLC), although the more ambitious TeV collider designs will require gigatron or its equivalent.

Proposed conclusion in 1995.

We propose to continue the present effort through the first six months of the extended program (through July 1995) with the specific objective to build and test a round-beam microwave-modulated cathode, shown in Figure 1-6. The cathode could either form the precursor to further development of microwave power tubes or be used as a stand-alone modulated cathode for linacs. We are seeking funding from other sources to continue cathode development and the gigatron thereafter.

We began the gigatron development in 1988, with an objective to build a prototype power tube in three years. Our progress towards this goal has been paced by the first step: fabrication of the gated field-emission cathode. Fabricating a submicron cathode structure suitable for microwave modulation is a very difficult technology. Many groups have striven towards this goal for other applications and finally abandoned it as unachievable. We have advanced the state-of-the-art in several important respects: we have invented two quite different designs for such a cathode, each of which has far better intrinsic performance for microwave modulation than any previous design; and we have developed fabrication processes by which we have succeeded in building and testing actual cathodes of each design. It has taken six years to achieve what we first projected would take two years. For some comfort in this regard, we note that the first pioneering steps in gated field-emitter cathodes by Spindt took twenty years from concept to practical display devices. It is a difficult technology.

At the same time, we are of course aware that progress has been continuing in the improvement of conventional approaches to the RF drive requirements of linac colliders. Improved designs for both arrays of conventional klystrons and relativistic klystrons have demonstrated the capability to deliver 100 MW power at 12 GHz, the frequency of choice for NLC. We therefore are proposing a terminal extension of this task of our DOE grant, aimed at the limited objective of

demonstrating microwave modulation of a round-beam gigatron cathode. Such a cathode would provide the basis for subsequent development of gigatron and other microwave power devices. It would also provide a directly modulated cathode for linacs.

We are encouraged by our progress, and frustrated by the time consumed in solving the myriad problems in process development and device physics and the remaining challenges facing us. We plan to continue development of the gigatron technology for applications to microwave power, pulse-modulated cathodes, and flat-panel displays. We will seek funding from other sources as appropriate. We cannot justify continued funding under the AARD program beyond the proposed milestone, in light of the improving performance of conventional RF power sources for NLC needs.

Figure 1-1. Isometric view of gigatron concept: gated field-emitter cathode; ribbon beam geometry; traveling wave coupler.

Figure 1-2. SEM image of a knife-edge cathode, showing the knife-edge and substrate, the polyimide dielectric, and the gate metalization flanking the emitting edge.

Figure 1-3. SEM image of a second-generation OPS cathode, showing the emitting surface, the current feed line, and the thin gate metalization over the pores.

Figure 1-4. Detail of gated field-emitter cathode and resonant input coupler.

Figure 1-5. Transfer function for several OPS triodes. This is the first observation of triode operation of an OPS field-emission device.

Figure 1-6. Round-beam gigatron cathode, configured for coaxial 50-ohm modulation.

2. 1994 Progress Report

A. Porous Silicon Cathodes

In mid-1992, we began investigating the possibility that an electron beam could be extracted from a porous silicon layer. This work was motivated by a remarkable discovery⁷ by Y.K. Yue, then a E.E. graduate student at Texas A&M, that such layers exhibit a copious current when configured as a diode, where a surface metalization forms the anode and the substrate silicon forms the cathode. Currents of $\sim 100 \text{ A/cm}^2$ were achieved, and the I/V characteristic exhibited the Fowler-Nordheim dependence characteristic of field emission. The physical origin of the emission process was unclear, and indeed is still a subject of debate and experiment. We set out to study the dependence of the field-emission performance on the fabrication process used to create the porous layer, and to attempt to develop a triode geometry in which the thick anode of a diode would be replaced by a thin gate metalization which could be used to extract the emitted electrons into the vacuum.

Porous Silicon.

Porous silicon was discovered in the 1950's by Uhlir and Turner¹⁰ while studying the electropolishing of silicon wafers in dilute hydrofluoric acid (HF) solutions. Within a range of process parameters, the silicon is anodically etched to form a dense array of pores. The pore diameter can be varied over the range $100 \text{ \AA} - 5 \mu\text{m}$, and the pores can be etched to form continuous parallel channels through a layer thickness from $\sim 1 \mu\text{m}$ all the way to the entire thickness of a wafer ($300 \mu\text{m}$). Figure 2-1 shows an electron micrograph of one particular porous layer¹¹ which is produced by seeding the etch process, as discussed below. Figure 2-2 shows an STM micrograph of the surface morphology of a porous layer.

Formation of porous silicon is carried out by anodic oxidation in HF as shown in Figure 2-3. The silicon wafer is connected to the positive terminal of a power supply so that it serves as the anode; a platinum electrode is connected to the negative terminal. The chemical reactions have been studied by several researchers¹². In concentrated HF, the silicon is etched at the surface by the reaction

where h represents a hole, e an electron, and $n < 2$ is determined by conduction band and valence band efficiencies. SiF_2 is an unstable substance; it reacts with HF to form silicic acid (H_2SiF_6) and hydrogen gas.

The role of holes is essential in the anodic reaction. In P-type silicon, where the majority of carriers are holes, the reaction can be carried out easily. In N-type silicon, however, holes must be otherwise introduced in order to carry out the reaction. One way to do this is to illuminate the surface: light with $\lambda < 1.2 \mu\text{m}$ can produce $e-h$ pairs in silicon. High-intensity illumination can be used to produce a large hole density near the surface. Another way to generate holes is to apply sufficient voltage to the electrodes to cause avalanche breakdown in the space charge region.

During the anodic dissolution, a porous layer is formed on the surface of the wafer. A model of this process was developed by Memming and Schwandt¹³ and later by Unagami¹⁴:

- the Si surface is covered with F⁻ ions;
- when an electric field is applied across the Si-electrolyte interface, holes move towards the surface;
- as holes reach the surface, they are trapped on the Si-Si bonds, weakening them;
- Si-F groups form at the surface, and dissolve into the liquid;
- F⁻ ions occupy the holes and release the charge;
- an insoluble surface porous film forms from the deposition of elementary Si during the initial anodization;
- the dopants are leached from the side walls so that the anodic reactions can occur only at the base of the pores.

A wide variety of pore sizes, geometries, and electrical properties can be achieved by varying the critical process parameters: dopant type and density, exposed crystalline plane, current density of anodization, and electrolyte chemistry. As two examples, Figure 2-1 shows an SEM image¹¹ of porous silicon with ~1 μm pore size, 100 μm depth, and extremely regular pore configuration; Figure 2-2 and Figure 2-3 show the surface of a porous layer with pore size ~100 Å, depth ~1 μm , and complex interconnected configuration. The former layer exhibits little field emissivity, while the latter is the most copious field-emission diode ever tested (700 A/cm² at 10 V). The microphysics of the emission process is still the subject of conjecture and experiment.

In the past two years, we have overcome several major milestones in the maturation of this technology. Eight months after beginning our work on oxidized porous silicon field-emitting devices (OPSFEDs), we developed the world's first successful process for fabricating gated field emission triodes from oxidized porous silicon. The results from these devices were extremely encouraging, and warranted further study of the technology. The greatest problem for gigatron performance has been the extremely large gate current which accompanies the emission into vacuum - typically 1,000 times greater than the emission current!

In the past year, we have successfully overcome one hurdle after another to develop a second-generation gated field emission cathode, more suited to the required frequency modulation and power gain. At the time of this writing, the very first of the second-generation devices have been tested. One of these has achieved an emission current equal to the gate current - a dramatic improvement which moves us closer to performance which would be suitable for microwave modulation experiments. Such experiments were the objective of this year's program; we are ~6 months behind our schedule in achieving this milestone with the porous silicon cathode.

In the next year, we plan to execute a careful optimization of the technologies involved in device fabrication. During the balance of 1994, we plan to concentrate our development on the reduction of the gate current which accompanies collector current. The ratio I_g/I_c varies dramatically from sample to sample as we vary the process parameters with which we fabricate the porous layer and its gate metalization. It is critical to understand the origin of the interception and of the dependence on fabrication and geometry if we are to achieve useful microwave modulation.

Figure 2-1. SEM image of a deep porous layer, in which pore etch was initiated by cone seeds and illumination; from Ref. 11.

Figure 2-2. STM image of the surface of an OPS triode, showing the thin gold metalization and the irregular pore apertures: top view.

Figure 2-3. STM image of the surface of an OPS triode: angle view.

Figure 2-4. Diagram of the anodization process for porous silicon fabrication.

1993 Achievement: True Gated Field Emission

Since the development of the OPSFED by W. K. Yue⁷ in 1989, no method for achieving stable three-terminal operation of a porous silicon field emission device had been successful. A vacuum diode configuration fabricated in 1990 by V. Madduri managed to produce up to 19 μA of current across a 2 μm vacuum gap. Nearly 100 V was required to produce this current, however. Using a true gated triode, we were able to produce 40 times the emission current across 1000 times the gap with only one-fifth the applied bias.

A major challenge this year was to achieve gate modulation at the porous silicon surface without obscuring the tiny (~ 100 Å diameter) pore apertures. For this purpose we adapted a cryo-evaporation process developed by Jaklevic¹⁵ at Ford Motor Research. If gold is evaporated onto a substrate at room temperature, up to a layer thickness of ~ 500 Å the gold is highly mobile on the surface and tends to a pattern of isolated clusters rather than a uniform film as the lowest energy configuration. In order to produce a uniform film for thinner layers, it is necessary to reduce the temperature so that the configuration mobility ($\sim e^{-u/kT}$) is reduced. Once a uniform layer has been deposited, the film is stable and will persist after the device is warmed to room temperature. One of the major achievements of the TAMU group for 1993-1994 was the successful commissioning of an ultrahigh vacuum (UHV) cryoevaporator, enabling us to apply ultrathin conductive gold layers onto our OPSFED samples.

First-generation triode tests.

The majority of the 1992-1993 research was conducted with $\langle 100 \rangle$ -oriented p-type substrates with resistivity of .001-.003 $\Omega\text{-cm}$. For comparison, some $\langle 111 \rangle$ substrates with resistivity of .005-.011 $\Omega\text{-cm}$ were also studied. N-type $\langle 100 \rangle$ substrates with a resistivity of .001 $\Omega\text{-cm}$ were also studied at the outset of the research. Inconclusive results were obtained for these samples, and more work on n-type substrates is planned.

Anodization current density was varied in the range 10-130 mA/cm^2 . Most of the samples were anodized for 10 seconds, but a few were anodized for 5 seconds to measure the effect on cathode emission of shorter anodization time. The anodization electrolyte was 3 parts 48% aq. HF to 1 part absolute ethanol. The majority of the samples were oxidized in ambient dry O_2 at 850°C for 45 minutes. Several of the samples were oxidized for 1 hour. Over eighty samples in all were made and tested. They were shadow-coated with 2000 Å of aluminum to form OPSFED's. The transfer function of the devices was measured with a Tektronix Type 575 curve tracer. Scope traces of the transfer functions were taken, and this I-V data was used to evaluate the relative performance of the devices. Fowler-Nordheim behavior was seen in over 65% of the samples fabricated.

Normally a set of 12 devices are tested from each sample wafer. The first four are destructively tested to determine their maximum output current and to get an idea of the operating voltage of the set. For the rest of the devices, the voltage is measured at several emission current levels within the operating limits of the set. It is seen that the operation of the devices is uniform within the set. Operating voltage of the devices ranged from a few volts to in excess of 180 V. Fowler-Nordheim emission current was measured from .1 mA to well in excess of 200 mA.

Transconductance of the devices varied widely, and the exact parameters that control the transconductance are not yet perfectly understood. High transconductance is a priority for microwave modulation. We began experimenting with the HF concentration and the resistivity in 1994. The most ideal diode behavior in an OPS device to date was discovered in early June 1994. Figure 1-5 shows the Fowler-Nordheim plot of the device.

It was hypothesized that the ultrathin gate layer would enable us to apply an electric field to the porous layer, sufficient to produce and modulate field emission, without intercepting the current at the surface, so that the device would function as a cathode to control emission directly into vacuum. This hypothesis was proved to be valid. The utilization of the gate layer resulted in a triode which produced .8 mA of vacuum emission current across a 3 mm vacuum gap. Only 20 V of gate bias was required to produce the emission, as shown in the Fowler-Nordheim plots shown in Figure 2-5. The deviation from a characteristic Fowler-Nordheim is roughly what one expects from the space-charge potential of the gate current in the pores. 200 V of collector voltage was sufficient to saturate the plate characteristic (Figure 2-6).

The geometry used to produce the proof-of-principle OPS triodes was very simple and had a large parasitic capacitance. Therefore the modulation frequency of the devices was limited. Nevertheless, 5 MHz modulation was readily achieved. Oscilloscope traces of these results are presented in Figure 2-7.

Figure 2-5. Fowler-Nordheim plot of the triode emission data of Fig. 1-5.

Figure 2-6. Plate characteristic of the above OPS triodes.

a. 200 kHz.

b. 1 MHz.

c. 5 MHz.

Figure 2-7. Modulated emission of electron current from an porous silicon triode. Top trace is gate voltage; bottom trace is emission current through a 10 k Ω resistor.

Lessons from the First OPS Triodes: Basis for the Stage II Design

The encouraging results from the first-generation OPS triodes were accompanied by some results indicating the necessity of further development of the technology. The construction of the first devices, as mentioned above, had a very simple geometry, in which the porous layer was surrounded by native silicon with a thin oxide layer on its surface. Figure 2-8 is a cross-section schematic of the fabrication process of the proof-of-principle triodes. Figure 2-9 shows the mounting scheme for the devices. In order to make contact with the thin gold gate, it was necessary to apply a patch of conductive epoxy over an area of the actual cathode. This imposed an intrinsic gate interception, and made the effective emitting area somewhat problematic to characterize. As shown in Figure 1-5 and Figure 2-10, there was a 1000 to 1 ratio in gate current to emission current. In addition, the planar region surrounding the gated region presented a large parasitic capacitance (~ 100 pF) which compromised efforts to achieve microwave modulation.

The lack of a well-defined emission area resulted in the loss of a firm number for the actual transmitted emission current density, but the use of the particular gate connection method allowed the measurement of emission current density produced within the OPS matrix. In excess of 700 A/cm^2 was measured on a .5 mm gate connection at 1% duty cycle. We estimate a transmitted emission current density into vacuum of 10 A/cm^2 .

Figure 2-8. Fabrication process for first-generation OPS triodes.

Figure 2-9. Mounting procedure for first-generation OPSFED cathodes. A tubular collector was located ~3 mm from the cathode to complete the test circuit.

Figure 2-10. I-V characteristic of the triode gate current.

Figure 2-11. Fowler-Nordheim plot of the triode gate current.

Process Development for Stage II Cathodes

In order to improve the frequency response of the second-stage OPS cathode, Smith developed the process outlined in Figure 2-12. The so-called "Stage II cathodes" have a parasitic capacitance of less than 20 pF, and allow operation to higher frequency than the first stage devices. In addition, flanking 1 μm -thick feed lines should provide a well-defined emission area, all-metal construction, and uniform biasing of the ultrathin gate layer (this last point has proved to be somewhat problematic in practice, as discussed below). During the first half of this year, all steps of the Stage II cathode fabrication process have been successfully completed in our clean room facility:

- Anisotropic etching, also called orientation dependent etching (ODE) is used on $\langle 100 \rangle$ -oriented substrates to form a series of "mesa" structures. This process has been perfected by the group in the development of the knife-edge cathode structures. Polyimide (PI) spin-on polymer dielectric is then applied, soft baked, and cured.
- A computer-controlled PI curing oven was built and commissioned during early 1994. It enables us to maintain tight control on the PI curing cycle, giving excellent reproducibility, high film density, strong adhesion, and no cracking.
- The cured PI is etched in a Tegal 211 barrel plasma etcher until the silicon mesas are exposed. This step was a key improvement in the Stage II process, and has been perfected. After PI etchback, an MRC Sputtersphere is used to apply an adhesion layer of titanium/tungsten and a 1 μm gold film to the entire surface. An image-reversal process is then used to remove the gold film and its adhesion layer from the OPS mesas which will be the active area of the cathode. Perfection of this process was a second major process achievement during the past 6 months. Figure 1-3 shows a Stage II cathode after this process step.
- The exposed silicon mesas are then anodized, using the gold feed lines and PI as etch mask. The gold feed lines are formed between the mesas, and the PI greatly reduces the parasitic gate/substrate capacitance in the finished device. The gold and PI form an HF-resistant mask for patterning of the porous silicon (PS).
- The anodization process is used to produce a porous layer $\sim 1 \mu\text{m}$ thick on the mesas. The anodization of anisotropically etched features provides a higher effective anodization current density than that for anodization of planar surfaces. A low-temperature oxidation cycle is then used to convert the PS to OPS. The PI curing oven is used for this purpose.
- The gate layer is deposited in the final process step, using our cryogenic evaporator system. By evaporating a film of gold onto a substrate at 77 $^{\circ}\text{K}$, Jaklevic showed that a uniform layer can be achieved even with film thickness of $\sim 50 \text{ \AA}$.

Figure 2-12. Process outline for second-generation OPS cathodes.

Preliminary Results from Stage II Emitters

Figure 2-13 shows a cross-section SEM of a completed second-generation OPS cathode. At the time of this writing, the first devices resulting from the Stage II process have been tested. Vacuum triode emission has been obtained. Emission from the first batch of devices was unstable, as with the first generation devices. The devices could not be conditioned to sustain emission at low gate voltage. The triode characteristic exhibited the same 1000:1 ratio of gate to collector current, which would be useless for microwave devices. Figure 2-14 shows a micrograph of a cathode following attempts at conditioning. The regions immediately flanking the feed line have burned along each side: we are producing a fatal level of local Joule heating. We interpret this heating as being due to the large gate current producing a voltage drop on the thin gate metalization, so that only the region immediately adjacent to the feed line receives the full gate voltage. Unless we can find and remove the origin of the large gate current, the OPS cathode will not provide a useful cathode technology.

A second batch of devices produced one sample which exhibited a 1:1 current ratio: the gate current was 1000 times smaller than before, with roughly the same collector current.

The relation of OPS emission to process fabrication

Field emission from porous silicon films has been observed over a wide range of porous silicon formation conditions. An initial parametric search conducted by Smith was targeted at relating device performance to the anodization current. Turn-on voltage of the devices was observed to increase with increasing anodization current density. Shorter anodization times resulted in lower turn-on voltages for the devices. $\langle 111 \rangle$ -oriented substrates were seen to give lower turn-on voltages and higher emission currents than comparable $\langle 100 \rangle$ -oriented substrates. $\langle 111 \rangle$ substrates are not well-suited for anisotropic etching of capacitance-reducing structures, so therefore more consideration was given to $\langle 100 \rangle$ substrates.

The results of parametric morphology studies from the literature show that the pore depth is linearly related to the anodization time, and that larger anodization current density results in larger pore diameter¹⁶. The results of these morphology studies combined with the results of Smith's electrical characterization studies give a first-order picture of the emission mechanism.

The electric field in the porous matrix is parallel to the pore walls in the body of the matrix. This field is distorted and enhanced in the neighborhood of the pore tip. The shallower OPS layers start with a stronger electric field, and thus require less voltage to initiate emission. Layers with larger pores have less electric field enhancement in the pore tip region, and thus require larger voltages for emission.

The small pore size associated with degenerately doped silicon (on the order of 10 nm) makes detailed study of the porous morphology exceedingly difficult. The actual formation mechanism of PS in p-type silicon is still poorly understood. The morphology change associated with the oxidation process has not been extensively studied, and greatly impacts the final OPS morphology. The role of pore branching and the effect of crystal orientation on emission are further considerations for a full understanding of this phenomenon.

Optimization of the gate transmission.

Stimulated by this latest result, we are now proceeding to a systematic study of gate interception and its link to the fabrication process. Good transmission requires that the morphology of the OPS layer be matched to the gate layer. The second-generation OPS field-emission cathode should enable us to achieve such a match. It provides a well-defined emission area, from which emission current density can be precisely measured. Good separation of the feed line areas ensures that all gate current in the device is due to a mismatch of pore size and film thickness or to intrinsic features of the electron transport in the pores. For transmission, the most crucial steps in the process are those in which the flanking gold feed lines are formed and the thin gold is deposited over both the porous layer and the feed lines. Our work to date suggests that the contact between feed line and thin gold is intermittent, and may be the cause of both the poor gate transmission and the local heating. We are currently trying several modifications to the process aimed at extending the thick gold feed line slightly onto the porous region to provide a more robust junction between the two metalizations.

One such modification would utilize the etch seed process of Lehmann¹¹. A pattern of dots is defined lithographically on the wafer surface, on a pitch of $\sim\mu\text{m}$. The dots are used as a resist mask for an initial ODE etch process, which produces conical depressions in the wafer surface. The electric field in the Si concentrates at these sites, so that the etch process proceeds preferentially there and produces a pattern of extremely straight pores. This process has been used by Lehmann to produce highly regular arrays of large-size ($\sim 1\ \mu\text{m}$) pores (Figure 2-1). We plan to measure emission from smaller-size pores made using the same procedure for regularization. The removal of brachiation should reduce the gate interception problem.

Figure 2-13. SEM cross-section of a completed second-generation knife-edge cathode.

Figure 2-14. SEM image of the OPS region surrounding the feed line on a second-generation cathode after testing.

B. Knife-Edge Cathodes

For the past 35 years, a number of investigators^{6,17} have developed several approaches to the fabrication of sub-micron field-emitting tips and associated gate structures as the basis for vacuum microelectronics. The motivation is simply stated: if the size of an emitting cathode could be reduced to submicron scale, and if a gate electrode could be configured above the cathode with a comparable spacing, then a few volts of modulation would suffice to control field emission. Since the transit time from cathode to anode also scales with the gate spacing, such devices should exhibit large bandwidth. Appendix C (Dr. Lee's Ph.D. thesis) presents a detailed history of the development of these devices and the process technology employed.

The most successful approach to field-emitter cathode fabrication has been that of C.A. Spindt⁶, who uses a sequence of etch and directional evaporation steps to grow a conical tip inside a $\sim\mu\text{m}$ aperture in a gate metalization. Figure 2-15 shows an SEM micrograph of his tip arrays. The tips exhibit uniform size and geometry, and large arrays have been operated with long lifetime at currents of up to 1000 A/cm^2 .

Importance of gate/base geometry for microwave modulation.

For tip arrays made using Spindt's technique, the gate aperture and the spacing of the gate to the tip have a natural scale which is tied to the thickness of the dielectric layer beneath the gate: for a dielectric layer of $1.5 \mu\text{m}$, necessary for adequate dielectric strength, the gate opening is comparable. This limits the field concentration which can be created at the tip, while producing a large parasitic capacitance between the gate layer and the substrate. These features of tip arrays are of little consequence for the display applications for which they were first developed, but present a major limitation for microwave power applications.

Figure 2-16 shows the key features of the tip geometry and of our knife-edge geometry which govern microwave modulation (see Appendix A). The figure of merit for high-frequency modulation is the ratio of the emitted current to the drive current required to produce the necessary voltage modulation:

$$\frac{P_{\text{out}}}{P_{\text{in}}} = \frac{I_e V_e}{I_s^2 Z_s} = \frac{A E^2 e^{-B\phi^{3/2}/E} V_e}{(\omega C_s V_s)^2 Z_s}$$

The electric field at the tip and the gate capacitance are

$$E_s \approx V_s / r, \quad C = \epsilon p^2 / s$$

where $r \sim 0.5 \mu\text{m}$ is the radius of the tip, s is the gate/substrate spacing, and p is the distance between tips in the array. Since $r \sim s/3$ and $p \sim 5r$ are practical limits for the Spindt fabrication approach, the "gain" depends upon tip radius as

$$\frac{P_{\text{out}}}{P_{\text{in}}} \propto s^2 / r^2 p^2 \sim 1 / r^2$$

We have devised a means to fabricate knife-edge arrays in which the knife-edge is flanked by a gate metalization with a control gap $g \sim 0.2 \mu\text{m}$, a knife-edge radius $r \sim 200 \text{ \AA}$, and a gate/base spacing $s \sim 8 \mu\text{m}$. The analogous dependence of "gain" on these parameters is roughly

$$\frac{P_{\text{out}}}{P_{\text{in}}} \propto s^2 / g r.$$

The enhancement in microwave gain should be a factor of $\sim 10^3$. A more detailed presentation of this analysis is contained in Appendix C; this summary demonstrates our motivation in developing the knife-edge cathode with small gate/edge control gap and large gate/base spacing.

The fabrication of such a device presents a major challenge. Were we to try to use lithography and etching directly to create the gate/base geometry, it would require submicron lithography at the limit of what is achievable in the best chip-industry equipment. Dr. Lee devised a clever alternative, described below, which achieves this geometry in a controlled, reproducible process, using the relatively old fabrication equipment which we have been able to assemble in our laboratory.

Figure 2-15. An array of gated field-emitting tips, fabricated by C.A. Spindt (Ref. 6).

Figure 2-16. The key features of device geometry for a Spindt tip array and a knife-edge array.

Knife-edge cathode fabrication process.

Figure shows our fabrication process for producing an optimum emitter structure. Each of the thin film process techniques is described in detail in Appendix C, chapters V and VI.

- 1) Pattern the SiO_2 mask on a (110) silicon wafer using standard photolithography technique. The mask pattern has groups of parallel lines with identical line width. The lines are accurately aligned with one of the two (111) planes that are perpendicular to the wafer surface.
- 2) Use an ODE process¹⁸ to etch out a perpendicular wall structure ($\sim 8 \mu\text{m}$ high) on the wafer. Each wall corresponds to a SiO_2 mask line. The wall typically has an aspect ratio $\sim 600:1$ if the resist lines are accurately aligned along the (111) crystalline direction. (Figure 2-18)
- 3) Apply a Dash-type etch¹⁹ to convert the walls to knife-edges. A $\sim 6^\circ$ slope can be formed, sharpening the rectangular prism to a knife-edge at the top. (Figure 2-19)
- 4) Further sharpen the edges by a low temperature oxidation process²⁰. The thickness of the oxide is in a range of $0.1\text{--}0.2 \mu\text{m}$. (Figure 2-20)
- 5) Apply a layer of polyimide (PI) coating²¹. The thickness of the PI layer ($\sim 10 \mu\text{m}$) should be greater than the height of the knife-edges so that the surface is planarized. (Figure 2-21)
- 6) Etch back the PI layer to expose the wedges. A plasma etch is needed for this process. We had to develop a laser diagnostic method (Figure 2-22), in order to accurately signal the moment when the knife-edge is first exposed above the PI surface; we can then precisely control the final height of the silicon knife-edge above the gate metalization.

- 7) Deposit the gate metal layer (Au). We have used magnetron sputtering and a Ti:W adhesion layer to produce a uniform .5 μm gold metalization with excellent adhesion to the PI surface. (Figure 2-23)
- 8) Apply spin-on photoresist, and etch back to expose the raised mounds in the metalization over the knife-edges. (Figure 2-24)
- 9) Wet-etch the exposed metalization so that the top of the SiO_2 wedge is exposed.
- 10) A buffered HF solution is used to remove the SiO_2 from the top and sides of the knife-edge, exposing the finished Si knife-edge. The gap separating the knife-edge from the gate metalization has been controlled by the thickness of the thermally diffused SiO_2 layer, which can be controlled with extreme precision to any desired value in the range 0.05-2 μm . (Figure 2-25)

The process outlined above has the following features:

- The process is self aligned. Only one lithography step is needed to produce the emitter and the gate. The finished structure has the emitter edge sitting right at the center of the gate gap.
- The oxidation process (step 4) serves dual purposes: It sharpens the emitter edge, and it defines the gate-to-emitter spacing. Silicon thermal oxidation can be very uniform and well controlled. This makes it possible to obtain a gate-to-emitter spacing anywhere around 0.1 μm .
- The size of the gate opening is independent to the emitter height. The process builds the emitter body before it makes the gate layer, and the gate metalization is separated from the silicon edge only by the thickness of the SiO_2 layer no matter how high the emitter is.
- The positions of the gate layers with respect to the emitter edges are adjustable. This is done by varying the emitter angle θ , the oxidation thickness, and the depth of PI etchback. In fact, geometric parameters like h, g, θ , s, and t are all adjustable in the process.

Figure 2-17. Fabrication process for knife-edge cathode arrays.

Figure 2-18. Rectangular prisms etched on 110 silicon using ODE.

Figure 2-19. Wedges formed by Dash etching the rectangular prisms.

Figure 2-21. Planarized layer of polyimide covering the wedges.

Figure 2-20. Thermally diffused SiO_2 layer in wedges.

Figure 2-22. Laser back-scattering diagnostic for end-point detection to etch PI layer until wedges are exposed.

Figure 2-23. Gold metalization on PI surface.

Figure 2-24. Etched metalization exposing SiO₂ wedges.

Figure 2-25. Final geometry, where SiO₂ has been etched back to expose knife-edge and gate.

Cathode tests.

We patterned 2" lithography masks to fabricate 16 1 mm² cathode arrays, distributed over the wafer surface. Each array contains two 15-line groups of 400 μm -long knife-edges and wire-bond pads for connection to gate and substrate. After fabrication, we diced the cathodes and mounted test specimens on a TO-5 header just as we did for the OPS cathodes. We then installed them in our test chamber and performed conditioning and emission experiments.

Figure 2-26 shows the emission characteristic measured on two cathodes from the same batch. Figure 2-27 shows a Fowler-Nordheim plot of the same data. In his thesis (Appendix C) Lee calculates the emission current from a line density of 100 emitting sites/ μm on a knife-edge of our geometry, assuming a work-function of 4.35 eV typical of silicon. The curves in Figure 2-26 show excellent agreement with the measured emission from each cathode. That is the good news.

The bad news is that the cathodes would typically develop shorts after a relatively brief period of operation (frequently only minutes), and arc over gate $\rightarrow$ knife-edge, destroying portions of the gold surface in the process. Figure 2-28 shows a cathode surface after such an arc. We found that the arcs were caused by a sub-microscopic ribbon of gold which commonly remained loosely attached at the bottom of a V-trench between the PI and the Si knife-edge. Figure 2-29 shows one such ribbon. The ribbons form because the PI etch forms a shallow V-groove at the PI-SiO₂ interface. The ribbons are only loosely attached, and wave around much like an electrometer when voltage is applied to the cathode.

After much painstaking investigation, it appears that the V-grooves are an unavoidable result of the plasma etch of the PI. Unless we can find an alternative process step which will eliminate the gold ribbons, it is unlikely we can make useful cathodes.

Process improvements to eliminate arc-over.

Happily, we have identified such a process and tried it successfully on a first batch of cathodes. Viehbeck (IBM) has perfected a technique²² in which he implants a PI surface to produce electrochemical bond precursors for metal bonds, and then performs electroless plating of Cu directly on the PI surface. The Cu surface is uniform, has small grain size, and is suitable for subsequently depositing either Au or Cr, either by sputtering or electroplating. Best of all, the Cu does not plate onto SiO₂, so that only the gate metalization is formed: no metal is deposited on the region where we currently have to etch it away.

Dr. Viehbeck's group has prepared a batch of our cathodes, in which they performed the above steps after we had completed the initial geometry of the knife-edge and PI. Figure 2-30 shows the result. The metalization is uniform and dense; there is no metal on the knife-edge; there is no V-groove in the PI, and no ribbon of metal adjacent to the knife-edge. The surface exhibits some micro-debris, which is an artifact of the IBM process environment and can be eliminated by conducting the fabrication in a clean-room environment.

We are currently setting up to test cathodes made using this technique. We have high hopes that it will prove to solve the shorting problem, so that we can begin to characterize the cathode performance.

Figure 2-26. Triode emission characteristic of knife-edge cathodes.

Figure 2-27. Fowler-Nordheim plot of knife-edge cathode response.

Figure 2-28. SEM image of a cathode surface after testing.

Figure 2-29. SEM image of a gold ribbon, formed in a V-groove at the knife-edge/PI boundary.

Figure 2-30. SEM images of Cu-plated knife-edge cathode.

3. Proposed 1995 Scope of Work

We propose to continue three activities in our cathode development through the first half of 1995: fabrication of knife-edge cathodes using electroless plating to eliminate the gold-shard problem; tuning of the OPS fabrication process to minimize gate interception; and construction of a round-beam cathode assembly as a stand-alone unit for 3 Ghz emission studies.

The IBM group is applying electroless plated metalizations to ten wafers on which we have carried through the cathode fabrication through step 6 above. The wafers have a sequence of relative heights of the knife-edge above the polyimide and of oxide thickness (gate gaps). We will select cathode arrays from each wafer, and prepare them for testing. We will seek to identify the optimum geometry for each of the above variables, and test the emission properties. We have demonstrated that the electroless process eliminates the metal shard which results when we etch a sputtered metalization; we hope to demonstrate stability against the breakdown which the shard produced on the sputtered samples.

We will tune the pore size and the pore geometry (straight vs. brachiated pores) in the Stage II OPS cathodes, and measure the emissivity and gate interception. We have recently completed a mask set which makes it possible for us to seed the pore formation on a regular pattern of sites by lithographically defining and etching a pattern of conical depressions in the Si surface, as discussed above. This process has been used by Lehmann¹¹ to produce such regular arrays of large-size ($\sim 1 \mu\text{m}$) pores (Figure 2-1). We plan to measure emission from smaller-size pores made using the same procedure for regularization. The removal of brachiation should reduce the gate interception problem. We are also studying the one cathode which operated without large gate interception to try to understand what differences in its morphology could explain the improved performance.

With the fruits of one or both of the above efforts, we plan to construct a cathode assembly suitable for mounting in a gun configuration. Figure 1-6 shows a cathode mount which brings the microwave modulation input in through a coaxial stem which is matched to present a 50 Ω load. A d.c. bias would be provided using an external d.c. block, so that the rf amplitude would turn emission on and off from an appropriate d.c. offset. The cathode assembly is designed to mount in our vacuum test stand. The rf drive, water-cooled collector, and microwave stem structure are on hand.

The cathode structure will be built in a fashion which makes it appropriate for mounting onto a diode for a test power tube, or as a free-standing modulated cathode for a linac injector. After initial tests at Texas A&M, we would plan to take it to Mission Research, who have developed a time-slice diagnostic capable of measuring beam emittance parameters as a function of time during an rf waveform.

4. High-Field Superconducting Magnets

As we strive to extend the high-field frontier for superconducting dipoles and quadrupoles, we must develop viable alternatives for two of the most fundamental ingredients of superconducting accelerator magnets that have served us so well for the past two decades: the NbTi superconductor and the $\cos \theta$ coil geometry. NbTi has no useful current-carrying capacity beyond ~ 10 Tesla. The only alternative today for pressing to higher field is Nb₃Sn, which extends j_c performance to ~ 18 Tesla. During the past decade the technology for producing high- j_c cable from Nb₃Sn has matured well, thanks to the programs at Brookhaven, Twente²³, Ansaldo, and LBL²⁴. We are only beginning, however, to master the techniques of winding, curing, impregnating, and collaring such coils for collider dipoles. To that end LBL is currently fabricating D-20, a prototype 13 Tesla $\cos \theta$ dipole using two inner shells of Nb₃Sn cable and two outer shells of NbTi cable. Figure 4-1 shows the cross-section of D-20. Figure 4-2 shows a coil subassembly being prepared for reaction bake. D-20 is currently being built and will be completed this winter and tested during Spring 1995.

The design and development of D-20 has already taught us a valuable lesson about the second major challenge: 13 Tesla is likely the limit for dipoles using the $\cos \theta$ coil geometry which has been the basis for all collider magnets used to date. In order to grade the conductor with decreasing field in the coil region, a multi-shell coil is used. The fragile strands of Nb₃Sn cannot accommodate keystoneing to conform to the cylindrical geometry of the $\cos \theta$ design. The coil placement of D-20 has been adapted to achieve the necessary current distribution using rectangular cross-section cable, but a total of four shells are required. While this approach should work for the 13 Tesla design field of D-20, extending the design to higher field would entail yet more shells, creating a coil package which is difficult to build, react, support, and maintain conductor tolerances. Pushing field strength to the limits of Nb₃Sn conductor will require that we develop an alternative coil geometry, which can achieve a greater effective packing fraction of conductor near the beam tube, produce the required field quality for collider operation, and be realistically manufactured. Happily a parallel set of developments at Texas A&M and LBL are converging on two concepts which have this potential.

Two years ago we invented the pipe magnet, a wholly new approach to high-field dipole design²⁵. Figure 4-3 shows a 13 Tesla design for the pipe magnet. The magnetic flux is guided by a coil distribution along the entire magnetic flux circuit, rather than by a coil clustered closely to each beam tube in conventional $\cos \theta$ designs. This approach conveys two important benefits: no stress concentrations (better mechanical support), and no persistent-current multipoles (fields do not fringe through the coil package). The invention of the pipe dipole resulted from our development of new calculation techniques for optimizing the design of structured coils²⁶, in which the coil shape and current elements are optimized to produce the best possible field quality subject to defined constraints on the coil boundaries and steel placement.

Following analysis of the pipe concept and the lessons from building D-20, the LBL and TAMU groups are beginning the joint development of several magnets which incorporate the de-

sign and fabrication innovations at both collaborating institutions. The TAMU program will focus upon primarily on the dipoles; the LBL program will focus primarily on the quadrupoles.

Magnet designs.

Figure 4-4 shows a **16 Tesla block-coil dual dipole**, which utilizes a block coil configuration and Nb₃Sn Rutherford cable. All coil elements are would as simple racetrack coils, with a novel provision for end winding which simplifies fabrication and provides improved end support. The block-coil design has the best magnetic efficiency of any high-field magnet, and provides for simple assembly and uniform coil prestress. The calculated fields exhibit multipoles which are less than one unit (10^{-4} cm⁻²) over a continuous 20:1 range of magnetic field. The calculated persistent-current sextupole hysteresis is 10 times smaller than in any cos θ dipole.

In the **pipe dipole**, the confinement of flux within the coil envelope uniquely makes it possible to use an inner coil element of tape conductor without the usual problems of AC losses and persistent-current multipoles due to penetration of fields through the face of the tape. The ability to use tape conductor would open two long-term possibilities for pushing still further the high-field envelope: Nb₃Sn tape has twice the critical current density j_c of cable conductor, and is amenable to using ternary components to enhance high-field j_c ; BSCCO tapes are now being fabricated in significant lengths with $j_c \sim 250$ A/mm² and critical field above 30 T.

We have also applied the block-coil approach to design a **330 T/m quadrupole** suitable for the low- β insertions at CERN's LHC. The design of the high-field quadrupoles for the intersection regions of LHC is a challenging task. A gradient of 250 T/m is required, with a 7 cm aperture. The block coil quadrupole would provide 30% greater gradient, operating at 4.2 °K.

Fabrication innovations.

The ends of a superconducting magnet have always been the hardest problem for design and fabrication and the most likely site for failure in operation. The coil elements for the above magnets are configured as rectangular coil packages, resulting in a considerable simplification of tooling, winding, assembly, and quality control. The ends of those coil elements which flank the beam tube must be bent out-of-plane to accommodate the beam tube, however. We have devised and demonstrated a procedure by which these coils can be wound as flat coils and then bent out-of-plane at the ends after winding, using a process which is used in industry for large motor coils.

All of these magnets feature realistic prestress strategy, copper stabilization suitable for realistic quench protection, and a design field distribution which maintains collider-quality uniformity over a 20:1 dynamic range.

The insulation system for Nb₃Sn magnets is another challenge for high-energy colliders, because the requirement of epoxy impregnation after winding severely limits heat transport in the coil package. We have devised an alternative insulation system, consisting of a resin-ceramic-glass filler. The filler is impregnated between the strands of the Nb₃Sn cable and E-glass cloth sock over each cable and soft-cured before coil winding. This system serves four important functions to provide stability to the fragile cable elements. The resin complex stabilizes the cable to prevent decabling during winding. The resin burns out and the glass component vitrifies during

the reaction bake of the Nb_3Sn coil to form a strong, inelastic matrix. The matrix supports the strands and prevents stress concentrations within the cable, fuses the E-glass tape to the cable, and electrically insulates each strand's surface. The ceramic component has a large heat capacity at 4.2 °K, contributing substantial stability against microquenches, and mechanically reinforces the glass after vitrification. The glass/ceramic mix does not fill the space between cable elements, but instead leaves an open porosity within the coil package for liquid helium to bathe the coil throughout similarly to B-stage for NbTi coils. These properties should provide an ideal basis for achieving mechanical support, electrical insulation, and thermal conduction within a Nb_3Sn coil.

We propose a multi-year R&D program, aimed to develop and test magnets of the above designs. The program couples calculations and simulations of the designs, development of core fabrication technologies, and construction and testing of short model magnets. **We plan to build and test two model magnets per year during the first three years.**

D20/7 @ 4.35K rectangular cable	Central Field (T)	I. L. Field (T)	O. L. Field (T)
6400 A	13	13.35	10.45
7000 A Short Sample	14.1	14.45	11.25
7000 A (Short Sample + 11% Degradation at 140 MPa)	14.1	14.45	11.25

Figure 4-1. Overall cross-section and detail of coil configuration for the D-20 Nb₃Sn dipole.

Figure 4-2. Completed D-20 coil subassembly prior to reaction bake.

Figure 4-3. 13 Tesla pipe dipole, showing the coils the cores, and the prestress collar.

Figure 4-4. 16 Tesla block-coil dual dipole, showing the rectangular coil structure, the iron housing, and the stainless steel inserts.

Introduction

The cost and performance of a hadron collider are largely determined by the field strength and field quality of its superconducting magnets. The dipole strength determines the circumference of the collider for a given beam energy; the dipole field quality determines the sustainable luminosity and the complexity of correction elements required in the collider lattice. The termination of the Superconducting Super Collider has dramatically demonstrated the need for ever-better technology to minimize the cost and maximize the performance of new high energy research facilities. Better magnet technology is required if we are ever to return to the challenge of an ultimate-energy hadron collider with more realistic cost and higher performance.

Conventional Superconducting Dipole Technology.

All conventional superconducting dipole magnets share a common design philosophy: the magnetic field in the beam tube is produced by a cluster of coil elements which surround the tube closely; the return flux circulates symmetrically around this cylindrical coil cluster and is guided in its circuit by a magnetic steel yoke far removed from the central bore. The field quality and magnet efficiency (ampere turns per Tesla) are determined by the configuration of the coil cluster. This philosophy can produce excellent results for field strengths up to ~ 10 Tesla. Figure 4-5 illustrates a successful 6.5 Tesla magnet - the $\cos \theta$ dipole for SSC²⁷. The frontier of conventional technology using NbTi superconductor is the 2-in-1 magnet for LHC²⁸ - a partially flux-linked $\cos \theta$ dipole pair shown in Figure 4-6.

Nb₃Sn dipole challenges.

As we press upon the high-field frontier, however, it is necessary to change from the relatively robust NbTi superconducting cable to the fragile, wind-and-react Nb₃Sn cable. At the same time, the performance of both the $\cos \theta$ and the superferric configurations deteriorates because the coil package becomes thick compared to the beam tube aperture. Figure 4-7 shows the calculated field distribution in a 4-shell $\cos \theta$ magnet similar to the LBL's 13 Tesla D-20 design. An increasing fraction of the ampere-turns are spent driving flux in circles within the coil package rather than producing field in the beam tube. The closure of field within the coil package produces stress concentrations in the coil package, and patterns of stress which are difficult to preload to prevent coil motion. Likewise the thick coil package develops a softer modulus, and precise positioning of coil elements becomes increasingly difficult. Figure 4-8 shows a design for a 13 Tesla superferric dipole, extrapolating the 6.5 Tesla design which was successfully built and tested by the Texas Accelerator Center²⁹, which suffers many of the same difficulties.

The block-coil design.

We have resolved both limitations by cutting the Gordian knot of high-field dipole design: we redistribute the coil to best advantage around the magnetic circuit, simultaneously producing an optimum dipole field in each of two apertures and returning the flux in a short path to achieve maximum magnetic efficiency. Figure 4-9 shows the calculated field distribution in a 16 Tesla

block-coil dual dipole. In addition to producing excellent calculated field quality over a wide dynamic range with minimum amp-turns, it offers a number of practical advantages for construction. All coil elements are arranged in rectangular pancake geometry, which is easy to wind with tight dimensional tolerance. Most coil layers have simple racetrack ends; even for the center layers which must be routed over/under the beam tube, we have demonstrated a simple technique in which they can be wound as racetrack coils and then bent out-of-plane at the ends. The rectangular coil geometry provides a particularly simple and effective means to provide optimum preload within a single laminated steel shell.

The pipe magnet.

During the past two years we have also developed a pipe dipole design, shown in Figure 4-3. The pipe dipole disposes the coil around the entire flux circuit, with the remarkable result that flux flows within the coil as water flows in a pipe. Figure 4-10 shows the field distribution: two uniform dipole regions are created within a suitably deformed toroid. Although the pipe dipole requires ~30% more superconductor than the block-coil dual dipole, it has one unique feature: field lines at the coil boundary are everywhere parallel to the coil surface. As a consequence, it is perhaps the only high-field magnet design which could be built using tape conductor for the inner coil elements without the usual problems of AC losses and multipoles due to a field component normal to the tape surface. The possibility of using tape conductor opens the world of Nb₃Sn tape (twice the critical current density of cable, and suitable for ternary additives to extend high-field j_c), other A15 systems which can only be fabricated on tape (e.g. Nb₃Al for fields to 23 Tesla³⁰), and ultimately perhaps for BSCCO³¹ (~30 Tesla at 10 oK). The pipe magnet has no known fundamental limitations up to a field strength of ~20 Tesla - three times the field of the SSC dipoles. Twenty-five years ago Kruger *et al.*³² demonstrated that compact quadrupoles can be successfully fabricated from tape conductor with controlled geometry on both body and end regions (see Figure 4-11). The pipe dipole may offer the opportunity of revisiting this approach for ultra-high field dipoles.

A block-coil quadrupole for low- β insertions.

We have also applied the block-coil approach to design a high-gradient quadrupole appropriate for use in the low- β insertions for the CERN LHC. The block-coil geometry is well suited to achieve a buildable, optimum geometry for a Nb₃Sn quadrupole. We have designed a symmetric quadrupole of the required aperture, which should produce a gradient of 300 T/m at 4.2 oK. The inner two quadrupoles of the LHC triplet have $\beta_y < \beta_x/4$. The block-coil design makes it feasible to design an asymmetric quad, shown in Figure 4-12, matching this 2:1 ellipse. It should produce a gradient (90% of short sample) of 330 T/m at 4.2 °K. This gradient is a 30% improvement over the best 1.8 °K NbTi designs to date - an improvement which translates directly into luminosity.

Significance for the U.S. high energy research program.

These magnet designs represent what may prove to be a true revolution in collider magnet technology. They uniquely open the possibility of fields of 16 Tesla or beyond for future hadron colliders. The development of a technology base for an ultimate 100 TeV hadron collider was cited as a priority for the U.S. HEP program in the report of the HEPAP Subpanel on Vision for the Future of High-Energy Physics. The need for fundamentally new magnet technology was

similarly highlighted in the report of the recent DPF Workshop on Future Hadron Colliders. The proposed long-term R&D program, a collaboration between LBL, Texas A&M University, and Japan, is the only effort which proposes to address this important frontier. Magnet efforts at Brookhaven are focused on RHIC and on transport lines for LHC; magnet efforts at Fermilab are focused on the Main Injector and on low-beta quadrupoles for LHC; magnet efforts at CERN are of course focused upon the preparations for construction of the LHC ring. **If there is to be a future for hadron colliders beyond LHC, we must engender a sustained, long-term program to develop a better magnet technology.**

We propose such a program. It is a collaboration between LBL and Texas A&M University; we are exploring possible interest at other institutions in joining the collaboration. The goal of the program is to explore alternatives for the superconductor and the coil geometry of collider magnets which would make it possible to at least double the current state-of-the-art performance. The programs at our institutions would focus on two complementary objectives:

LBL: (after D20 testing) block-coil quadrupoles;
Texas A&M: dipoles using block-coil and pipe geometries;

The program of work concentrates on building and testing short model magnets. It is only through such testing that any new magnet technology can be evaluated and matured. To this end, in the dipole program at Texas A&M we set ourselves an ambitious overall goal: **we will build and test at least two prototype dipoles each year.** The rationale for this program and a WBS schedule for the first-year program are presented below. The tentative agenda for the proposed 3-year renewal is:

Year 1:	NbTi block-coil dipole	BT-1
	Nb ₃ Sn block-coil dipole	BS-1
Year 2:	NbTi pipe dipole	PT-1
	Nb ₃ Sn block-coil dipole	BS-2
Year 3:	Nb ₃ Sn tape pipe dipole	PST-1
	Nb ₃ Sn block-coil dipole	BS-3

From the SSC, we propose to assemble a group of some of the finest and most experienced magnet personnel and a complete base of equipment for prototype magnet construction and testing. The personnel are prepared to join us immediately; the equipment is contained among the assets which have been transferred to TNRLC. Texas A&M has allocated a 20,000 sq.ft. high-bay building space which will comfortably house the activity. This combination of people, equipment, and facility uniquely makes it possible to engender a new magnet development activity and begin almost immediately building and testing magnets. It is the only combination which will retain these personnel and this equipment in productive activity to create a future for the U.S. high energy research program.

We will rely upon our collaborators for substantial help in many aspects of the dipole program. LBL will contribute ~6 months of effort by Dr. McInturff to supervise the transfer and re-commissioning of the SSC equipment at Texas A&M. LBL will fabricate all conductor required for the dipole magnet program. LBL will contribute teamwork and leadership in several design areas: persistent current fields, quench simulation, coil end supports, instrumentation³³, and cryostat design. During the first-year program, all model magnets will be tested in the cryostat which is being built at LBL for the D-20 tests; this enables us to defer the decommissioning of the test cryostat and ASST system until late in the first year without delaying the model program.

Figure 4-5. Cross-section of the SSC dipole: 6.5 Tesla, 5 cm bore, 4.2 °K.

Figure 4-6. The NbTi dual dipole magnet for LHC: 8.7 Tesla, 5 cm bore, 2 °K.

Figure 4-7. Calculated field distribution in the D-20 4-shell dipole.

Figure 4-8. Calculated field distribution in a 13 Tesla superferric dipole similar to the 6.5 Tesla design which was built and tested at the Texas Accelerator Center.

Figure 4-9. Calculated field distribution in the 16 Tesla block-coil dipole.

Figure 4-10. Calculated field distribution in a 13 Tesla pipe dipole.

Figure 4-11. A tape-wound quadrupole, built at Brookhaven National Lab in 1966.

Figure 4-12. Asymmetric block-coil quadrupole for LHC low-beta insertion: 330 T/m, 7 cm aperture, 4.2 °K.

A. Common Design Features

In order to get a complete picture of the evolution of the dipole field designs described above, Figure 4-14 shows a succession from the NbTi dipoles for the SSC and LHC, to the D-20 Nb₃Sn dipole, to the pipe dipole, to a block-coil version of the pipe dipole, to a variant of the block-coil pipe dipole, finally to the block-coil dipole. The progression is shown in that order because it is the order in which the designs were invented. While the pipe dipole was the first "new geometry" Nb₃Sn design in our work, we consider the block-coil dipole to be the first practical design in the succession which we propose to build and test in the development program. Several design considerations are common to all of our designs: basic field configuration, aperture, field quality, dynamic range, cable orientation, prestress strategy, and coil insulation.

Superconductor.

We have designed the magnets to use rectangular Rutherford cable, with fine-filament Nb₃Sn/Cu strand, similar to that being used at LBL for D-20. We may use a nickel coating (like ITER) to suppress a.c. losses; it would also provide a diffusion barrier for the "inorganic B-stage" insulation. The SC:Cu ratio is graded through the coil for optimum coil performance.

Basic field configuration.

The magnets of Figure 4-3 and Figure 4-4 share a major departure from the conventional $\cos \theta$ coil configuration: The coil elements are arranged in rectangular pancake coils flanking each beam tube, and a magnetic steel flux return is close-coupled just beyond the boundary of the rectangular coil region. This configuration provides optimum packing density, ease of fabrication, optimum prestress geometry, and a simple basis for tuning field quality.

Aperture.

The aperture required for hadron collider operation has been the subject of intense study for the designs of SSC and LHC. The issues determining aperture requirement were recently summarized at the DPF Hadron Collider Workshop. For a $\sqrt{s} = 40$ TeV hadron collider, a good-field aperture ($\delta B/B < 10^{-4}$) of 5 cm horizontally and 3 cm vertically is typically required. In a $\cos \theta$ dipole, the physical aperture is circular. The block-coil dipole has been scaled to provide a 5 cm cylindrical aperture with 10^{-4} field uniformity. In the pipe dipole, horizontal aperture can be provided with modest impact on amp-turns and overall size, while vertical aperture carries a more serious impact because of the necessity to carry the horizontal prestress load of the coil across the arch of the beam tube cavity in the winding core (see Figure 4-3). Happily this asymmetry parallels the aperture requirements. The 13 Tesla pipe design has therefore been scaled to provide a 5×3 cm² elliptical aperture with 10^{-4} field uniformity.

Dynamic range.

The dynamic range of a hadron collider (full energy/injection energy) is ~10:1 to 20:1. The injection field quality in a $\cos \theta$ dipole is limited by persistent-current multipoles which are created when currents are induced to flow between filaments in a strand as a magnet is ramped in field. This phenomenon is reduced by a factor of 10 in our magnets for two reasons: the conduc-

tor is further from the beam than in a $\cos \theta$ coil, and a magnetic steel pole piece presents a planar boundary above and below the beam tube region. As presented below, this boundary condition strongly suppresses persistent-current multipoles at low field. Both of our designs are designed to produce collider field quality over a 20:1 dynamic range.

Cable orientation.

In both of our designs, the cable elements are oriented so that the face of the Rutherford cable is parallel to the field axis. The parallelism is most dramatic for the pipe dipole (Figure 4-10). This provision provides a substantial reduction of AC heat losses when the magnets are ramped during acceleration. AC losses result mainly from currents which are induced to flow between strands within each cable element. Because the cables present their thin dimension to the magnetic flux, induction is minimized for a given inter-strand resistance. This benefit is in marked contrast to $\cos \theta$ designs, where most cable elements are oriented face-on to the magnetic flux.

AC losses.

As a collider magnet is ramped from injection to full field, eddy currents are induced between strands within a cable. The ac losses due to these resistive currents pose a limit to the rate at which a magnet can be ramped. In the DPF Hadron Collider Design Study, ac losses were projected to be a problem limiting performance of ultimate-energy colliders.

In both the block-coil dipole (Figure 4-9) and pipe dipole (Figure 4-10), the cable elements are oriented edge-on to the magnetic field. By contrast, in a $\cos \theta$ dipole the cable is oriented face-on to the field (Figure 4-7), and the field fringes strongly through the coil. The ac losses scale approximately with the projected width of the cable perpendicular to the field direction, so ac losses should be a factor of ten smaller than in $\cos \theta$ magnets. The actual ac losses will also depend on the inter-strand resistance. As part of our cable insulation system development, we plan to try to achieve a high-resistance coating on the strands without compromising j_c performance, using a thin Ni plating, similar to that being developed for the ITER conductor, wetted by the vitreous glass during reaction bake.

Prestress strategy.

As we design dipoles for 16 Tesla and beyond, and use brittle Nb_3Sn conductor for their coils, a primary challenge is to provide a sufficient preload to counter the Lorentz forces without unacceptable coil motion. The rectangular pancake coils of our designs accommodate a particular simple and effective prestress strategy: horizontal pistons from each side, and no necessity of an interleaved collar. The cable elements are oriented face-on to the preload forces, providing the stiffest possible modulus against coil motion.

Coil insulation.

Even with the elimination of stress concentrations, the Lorentz stress at 16 Tesla is immense - 170 MPa. We plan to develop a new approach to Nb_3Sn cable insulation; an "inorganic B-stage", which would provide micro-quench stability and inter-strand mechanical support. The approach is described in Section 5 and illustrated in Figure 4-13. It is similar to work done by Ceramphysics and Westinghouse²⁰, by Tanaka *et al.*³⁴, and by Schutz and Reed³⁵, in that it uses a glass/ceramic mixture to coat the strands of each cable element, providing both mechanical sup-

port and electrical insulation. It is different from both of the previous approaches in that the insulating mixture is applied in a green state in the cable before winding, in such a way that the final insulation (after the Nb_3Sn reaction bake) leaves open porosity in the spaces between cable elements. Liquid helium permeates this space, bathing the coil and providing enhanced enthalpy to stabilize against microquenches. Two experts in inorganic composite systems are collaborating with us to develop an optimum mixture which achieves this combination of properties.

Coil winding strategy.

In both designs, most coil elements are in the form of simple rectangular pancake coils, and can be wound as a racetrack in a particularly simple manner. The central coil elements which flank the beam tubes must be bent up and over the beam tube at each end, however. Historically the techniques for fabricating the ends of a coil are the "weak link" in the entire fabrication operation, and produce the highest likelihood of failure in the finished magnet.

We have devised a technique for winding racetrack coils, in which the entire coil package is completed as a flat pancake coil, and the ends are then bent up *as an assembly*. Figure 4-15 shows a mock-up coil of Nb_3Sn cable which has been wound flat, then bent as an assembly to clear a 5 cm. Beam tube. A very modest force is required (~ 10 N), and there is no damage whatever to the coil or its E-glass insulating sleeve. Two things happen in this approach which are actually helpful in preparing the end coil for collaring and prestressing. First, as seen in the picture, the geodesic of the bent coil actually flares out slightly, forming a hoop of somewhat larger radius than the actual inner spacing of the body coil. This both relieves the stress concentration which would otherwise occur at the interface between body and end regions, and reduces the magnetic field in the end coil. Second, the turns tend to pull together, removing the slight slack between turns in the end region, so that the bent coil end assembly is tight and forms an integral block to collar and prestress.

By using this simple, effective winding technique, all coils for the block-coil magnet can be wound as flat racetrack assemblies, and the central coil segments can be bent up as required. The winding process should be simple and amenable to precise dimensional control. For the pipe dipole, the coil in the toroidal region is comprised of fan coil segments, each of which is a 3:1 fan from a single inner layer to three contiguous outer layers, as shown in Figure 4-16. The coil segments for the dipole region would be fabricated using pancake coils as discussed above.

Nb_3Sn presents substantial challenges in fabricating long dipole coils. Because the coils must be reacted after winding, the coil must be configured for the $\sim 750^\circ\text{C}$ bake in a support fixture which matches closely the expansion of the cable. Figure 4-17 illustrates this problem in the case of D-20. Each coil section was wound tightly upon the end spacers as the layer was successively wound. In the bake, however, differential expansion between the (Al bronze) end spacers, the (Cu) body spacer, the base fixture, and the cable produced a relative elongation of the coil as temperature increased followed by a contraction as it decreased. Friction and the stiffened modulus of the coil after reaction apparently prevent the process from reversing itself during cooldown, leaving gaps in the coil/support space. Such gaps are not necessarily a problem, if one stuffs the gaps with fiberglass wadding and then impregnates the coil as LBL does. Since we plan to strive to achieve an "inorganic B-stage" insulation (see below), such gaps are more serious.

Figure 4-13. Schematic illustration of inorganic B-stage insulation strategy.

(a)

(b)

(c)

(d)

(e)

(f)

Magnet	Field Strength (T)	Store Energy (MJ/m)	Amperturns (MA)	Size (mm)	b2 (unit) @injection	b2 (unit) @collider
a. SSC dipole	6.5	0.105	0.585	O 330	2	2.0
b. LHC dipole	8.65	0.548	1.88	O 560	3	2.5
c. Berkeley D20	13.0	0.862	1.72	O 820	N/A	N/A
d. Pipe magnet	13.0	3.64	5.50	860*760	N/A	1.8
e. Hybrid magnet	13.0	2.23	4.50	O 500	N/A	2.0
f. Block magnet	16.0	4.36	5.39	O 500	0.4	-0.23

Figure 4-14. Evolution of dipole design, from $\cos \theta$ to pipe to block-coil. The parameters for the dual-aperture designs (b, d-f) are for both bores together.

Figure 4-15. Photographs of a mock-up coil of Nb₃Sn cable, in which the entire coil end has been bent up to clear a 5 cm beam tube.

Figure 4-16. Schematic illustration of the winding arrangement for one toroid coil segment.

Figure 4-17. Photograph of an inner coil of the D-20 magnet, after reaction bake.

B. Block-Coil Dipole

The block-coil dual dipole is configured as a window-frame magnet, in which the coil is divided into three segments so that the Nb_3Sn conductor can be graded to optimize $j_c(B)$. Figure 4-18 shows the load line for the three coil segments, designed to optimally utilize the superconductor throughout the coil.

Field quality and dynamic range.

The multipole content is dominated by two phenomena: the pairing of the two dipoles introduces an asymmetric reluctance which in turn produces a quadrupole; and the progressive saturation of the steel produces a sextupole and decapole. We have corrected these effects by introducing three modifications. First, the innermost coil is arranged on a contour which cancels the decapole and some of the sextupole (Figure 4-19). Note that the contour is antisymmetric: the coil profile is shaped on the inner boundary of the inner leg, and the outer boundary of the outer leg in each dipole.

Second, the three coil elements are gapped apart asymmetrically, to correct the reluctance asymmetry. The coils are spaced with minimum gap on the outer leg, but with substantial spacers on the inner leg. This cancels most of the quadrupole. shows the calculated multipoles which result when all three coils, thus configured, are excited by a common (series) current. While it is possible to achieve collider-quality field at full excitation, at low field substantial quadrupole (~ 40 units) and sextupole (~ 40 units) fields are produced, due to the transition of the steel from unsaturated to saturated state as field is increased.

The third modification is to operate the three coil segments with different currents. The currents can be programmed to cancel all multipoles to less than one unit (10^{-4} cm^{-n}) at all field strengths over a 20:1 dynamic range. Figure 4-20 shows the current programming $I_i(B)$. Figure 4-21 shows the multipole content as a function of field strength.

The choice of aperture is governed by several considerations. The aperture requirement for collider operation has been the subject of exhaustive scrutiny throughout the design of SSC and LHC. The subject was reviewed at the recent DPF Hadron Collider Workshop. The horizontal aperture requirement is dominated by the dispersion due to momentum spread at injection; for SSC it was 5 cm. physical aperture, 3 cm collider-quality field. The vertical aperture does not require accommodation of momentum dispersion; the same 3 cm. collider-quality field aperture suffices.

Persistent-current multipoles.

Two of the virtues of both the block-coil and pipe designs is the suppression of magnetization fields by the planar steel boundary, and the suppression of a.c. losses by the orientation of the cable elements edge-on to the field. We have calculated the multipole fields produced by magnetization currents within the superconducting strands, following the procedure of Caspi³⁶. Each coil segment is represented by a magnetization block, with a M/H magnetization curve appropriate to describe the measured magnetization properties of the actual superconducting strand.

This approach has been used to accurately reproduce the observed magnetization fields in Tevatron and SSC magnets. For Nb_3Sn cable, the filament size represents a somewhat uncertain parameter in estimating the magnetization curve: while the intrinsic filament size in the internal-tin strand which is used at LBL for D-20 is quite small ($\sim 2 \mu\text{m}$), the diffused tin between strands produces a weakly superconducting bridge at low current and field, equivalent to a much larger "effective strand size" at injection field. The low-field effective strand size is estimated to be $\sim 20 \mu\text{m}$ for the material currently in use. A magnetization curve appropriate for that strand size was adopted for our calculations.

Figure 4-21 shows the persistent-current multipoles calculated for the 16 Tesla block-coil dual dipole. The maximum sextupole hysteresis is ~ 3 units at $B_0/20$, one tenth of the b_2 at the same fraction of full field for an SSC dipole (Figure 4-22). We have included the calculated magnetization fields in a re-optimization of the current programming, and can again reduce all multipoles to < 1 unit over the full 20:1 dynamic range (Figure 4-24).

Current programming.

The block magnet requires current programming to achieve optimum field over a 20:1 dynamic range. We realize that current colliders utilize a single current bus for the main dipole family, and that many in the accelerator community have strong opinions that multiple current busses would pose a major risk to stable operation. Certainly a number of issues arise which must be evaluated quantitatively before a multiple-bus scheme could be seriously entertained for a future collider. However, all of the issues we have been able to identify appear to be readily manageable without substantial cost or risk.

The frequently cited need for independently adjustable orbits can be accommodated at the level it is required by means of a family of lumped correction elements in the spool pieces. The power supply stability and regulation requirements are well within commercial power supply technology. The quench protection design must be segmented in multiple parallel circuits for diode clamps, dump resistors, and heaters, so the segmentation would actually be a convenience. The accommodation of multiple current busses in the cryostat is a modest issue in the overall design. The only issue which we have identified which appears to need some near-term analysis is the potential for transmission-line modes propagating around the magnet ring, in effect shunting current among the three circuits in a differential traveling wave which might propagate with little attenuation.

Quench protection.

With a stored energy of 2.2 MJ/m in each dipole, quench protection is a critical consideration for reliable magnet operation. From the experience to date with quench protection of collider dipoles, the parameter which is of great importance in quench dynamics is the maximum current density j_{Cu} which would appear in the copper stabilizer of the cable during a quench. If $j_{Cu} < 1,100 \text{ A/mm}^2$, active quench protection can usually be designed to safely distribute a quench so that a magnet consumes its stored energy without overheating at any location. If j_{Cu} exceeds that limit, quench protection is usually very difficult, particularly for distributed strings of magnets which must be effectively isolated from one another so that a quench does not propagate from magnet to

magnet. We have adopted this limit in designing the SC:Cu ratio for all coil segments in our designs. Table I presents the parameters of all three coil segments in the block-coil dipole.

We are currently simulating the quench behavior of the block-coil magnet, using a modified form of the code QULHC³⁷. We have assumed a network of clamp diodes, limiting and dump resistors, and pulsed heaters as shown in Figure 4-25. The quench is assumed to initiate on an inner coil segment. The decay of current during the quench is shown in Figure 4-26; the decay time constant is ~ 0.2 sec. Figure 4-27 shows the total coil voltage (resistive plus inductive) across each coil segment during the quench. A maximum of 1,300 V is developed; the maximum voltage location is on the middle coil under the initiation condition studied. Figure 4-28 shows the maximum temperature as a function of time during the quench. A maximum of 430 °K is reached on the outer coil. These results are only the beginning of our study of quench dynamics in the block-coil dipole. The circuit parameters in Figure 4-25 have not been optimized, and the limits in temperature and voltage can probably be improved. We are experimenting with the segmentation and placement of circuit elements to that end. These preliminary results are already within reasonable bounds for a localized, non-destructive quench. They demonstrate that the 16 Tesla block-coil dual dipole can be adequately protected.

Prestress Strategy.

The total preload on each side required to counteract the Lorentz force is $F = S w = 22$ kT/m. The preload must be delivered to the side wall of each coil assembly. In this respect the block dipole is ideal for simple, effective preloading. Figure 4-25 shows two techniques for delivering the preload. The simplest approach is to divide the steel flux return at the top and bottom of its rectangular cavity, creating two pistons on the sides. The pistons are then pressed inwards in a press to the desired preload, and the outer seams between the pistons and the top/bottom pieces are welded to lock in the preload. It is hard to imagine a simpler way to deliver a controlled preload. The one disadvantage is that some fraction of preload would likely be lost in cooldown, due to differential contraction.

The second approach uses the differential contraction of Al and steel to advantage to deliver additional cold preload, in a fashion similar to that used at Brookhaven, SSC and CERN. The steel flux return is segmented at the bifurcation between the region where flux couples between the dipoles and the region where flux returns on the outside leg. In this way one eliminates any effect on field strength or homogeneity from any residual crack at the interface. A controlled gap is made between the steel segments, and bars of aluminum are placed at the top and bottom of the assembly to space the gap while the magnet is at room temperature. When the magnet is cooled to 4.2 °K, the Al bar shrinks more than the steel, and the gap closes, delivering additional preload to the coil. The preload would be delivered in this strategy by either banding or wire-wrap around the steel assembly.

Table 1. Superconductor properties in the coils of the block-coil dipole.

	inner coil	middle coil	outer coil	
effective filament diameter	20	18	18	μm
# filaments	1164	933	1289	
strand diameter	0.965	0.825	0.980	mm
# strands	34	19	13	
Cu/SC	1.0	1.15	1.3

Figure 4-18. Load line for the three coil segments of the 16 Tesla block-coil dual dipole.

Figure 4-19. Calculated multipoles in the block dual dipole: all coils operated in series.

Figure 4-20. Current programming of three coil currents to produce optimum field quality.

Figure 4-21. Calculated multipoles in the block dual dipole with current programming.

Figure 4-22. Calculated persistent-current multipoles from magnetization fields.

Figure 4-23. Measured persistent-current multipoles in SSC prototype dipoles.

Figure 4-24. Residual multipoles after re-adjusting the current programming to cancel magnetization fields.

Figure 4-25. Circuit used in simulation of quench protection for block dipole.

Figure 4-26. Current decay during quench in each coil segment.

Figure 4-27. Coil voltages during quench.

Figure 4-28. Maximum temperature in each coil during quench.

Figure 4-29. Two techniques for applying preload to the block dipole: a) side bars acting as piston; b) split flux return along flux bifurcation, and insert Al spacer for cold preload.

C. Pipe Dipole

The pipe magnet consists of two current sheets, configured roughly as a toroid, with insertions which produce a high-quality dipole field at two opposite locations for the two beams of a hadron collider. The design strategy is summarized in Appendix D. The real "magic" of the pipe magnet is the invention of a **flux transformer** which changes the field $\vec{B} = B_0(R/r) \hat{\phi}$ of the toroid sections into the uniform field $\vec{B} = B_0 \hat{z}$ of the dipole section. We have invented a particular deformation of the outer current sheet which produces the desired transformation²⁶. The collider field quality can be readily achieved in the dipole insertion without additional corrections. Addition of a modest pole face winding at the boundaries of each dipole section could be used to further reduce or tune multipoles.

Field optimization

Design of the pipe dipole has required both the use of a new software environment, OPUS, to optimize the geometry for the flux transformation, and a rather intricate meshing of the 2-D structure to adequately model the structure. Figure 4-24 shows the finite-element mesh which was used in PE2D to calculate the magnetic field distribution and forces.

Figure 4-10 shows the calculated magnetic field distribution for such a coil configuration. The optimization produces the following approximate guidelines:

- the mean radius of the toroid sections should be $\sim 5a$, where a is the radius of the beam aperture within which uniform field is required in the dipole section;
- the coil in the toroid section should have an integral ratio (typically 3:1) of outer to inner radius, in order to accommodate the flux transformer;
- the transition from dipole to toroid should include a tapering of current distribution, from the one limiting case to the other, with a modest flux leakage in the transition which must be compensated in the magnetic design.

Table 2 presents the calculated multipoles for the 13 Tesla pipe dipole. The design assumes cable conductor, similar to that used in D-20, with 3 graded current densities through the thickness of the coil. All 3 coil segments are assumed to be operated in series. A pole-face winding has been included at the interface between the center dipole insert and the U-shaped toroid inserts, in order to provide tuning of multipoles below the 10^{-4} cm^{-1} level. No analysis has yet been made of the error fields which would result from conductor placement errors. Such analysis will of course be necessary before arriving at a prototype design.

Figure 4-30. Mesh for numerical modeling of the pipe dipole in PE2D.

Table 2. Calculated multipoles of the 13 Tesla pipe dipole

n	$b_n (10^{-4} \text{ cm}^{-n})$
1	-.004
2	-.63
3	+.023
4	-.17
5	+.064
6	-.48

Tape conductor for the pipe dipole.

The pipe dipole is unique in the feature that the magnetic field in its bore circulates around the internal region, and does not fringe through the coil package. Comparison of Figure 4-10 with all of the other field geometries above shows that, uniquely in the pipe magnet, the magnetic field at the location of the conductor is everywhere tangential to the boundary of the coil package. If the coil were to be fabricated from tape conductor, there would be very little field component normal to the face of the tape. This feature is crucial to the possibility of building superconducting dipoles using tape conductor. While such dipoles have never been developed (although Figure 4-11 shows a tape-wound quadrupole from 25 years ago), they would open the world of inexpensive conductor fabrication for Nb_3Sn , and perhaps of practical conductors using high-field A15 systems and BSCCO.

The limiting consideration in using tape conductor is magnetization current which would be induced by time-changing magnetic flux through the face of the tape. In a tape-conductor pipe magnet, the flux would be oriented parallel to the tape face, and such currents would be largely avoided. This feature is vital from the consideration of j_c , field quality (persistent-current multipoles), and a.c. losses. Figure 4-27 presents data³¹ on the effect of magnetization currents in BSCCO tape if the magnetic field forms a significant angle α with respect to the tape-normal direction. j_c would be degraded by a factor of 3 if tape conductor were used in a $\cos \theta$ dipole ($\alpha \rightarrow 0^\circ$ at some regions of inner coil), by a factor of ~ 1.4 in a block-coil dipole ($\alpha \rightarrow 70^\circ$), and not at all in a pipe dipole ($\alpha = 90^\circ$ everywhere).

Current requirements.

The pipe dipole requires 5.5 MA turns of conductor, a little more than the block-coil dual dipole. If it proves feasible to use tape conductor, the actual mass of superconductor may be significantly reduced, however, since the high-field critical current in tape is typically $\sim$ twice as great for Nb_3Sn tape as for cable. The aggregate conductor mass would be governed mainly by the amount of Cu required for realistic quench protection.

GE has developed a continuous tape fabrication process for Nb_3Sn tape, and plan to work with LBL to develop and evaluate tapes with ternary alloys and artificial pinning centers (APC). Their process is a continuous-feed fabrication, beginning with a Nb (or NbTa, etc.) ribbon, which is coated with Sn in a dip process, then reacted in a fast high-temperature continuous-feed furnace, then clad to Cu stabilizer and insulating layer. The unit cost for fabrication of large quantities of conductor with this process is unknown, since it is now being used for a product for the first time - a 1 Tesla split solenoid for MRI during surgery. It appears likely, however, that Nb_3Sn tape conductor could prove to be substantially less expensive and higher performance than an equivalent cable.

Tape is the only process by which high-field, high- j_c performance has yet been achieved in Nb_3Al . Figure 4-25 shows the measured short-sample j_c for Nb_3Al tape which was fabricated using each of two continuous processes³⁰ in which the reaction is achieved using a laser and an electron beam, respectively. In both cases, $j_c \sim 200 \text{ A/mm}^2$ at 4.2 °K was achieved, with maximum field of ~ 23 Tesla.

Tape remains the best form in which to achieve high j_c and high B_c in practical high-temperature superconductors (HTS) such as BSCCO. Because the HTS mechanism involves conduction along ordered planes in the perovskite structure, orientation of grains in a continuous layer is of critical importance. This is more readily achieved in tape form than in wires. Figure 4-26 presents measured j_c vs. B for BSCCO tape³¹; $j_c \sim 200 \text{ A/mm}^2$ up to ~ 30 Tesla at 20 °K. The possibility of operating at higher temperature could become an important feature at an ultimate-energy hadron collider, because the synchrotron-radiation heat load will likely dominate the heat budget, and could dominate the entire power budget of the facility.

Prestress strategy.

Figure 4-28 shows the calculated pattern of Lorentz stress in the coil package of the 13 Tesla pipe dipole. The stress concentrates in the dipole coils, and drops by a factor of 10 in the

toroidal regions. We have designed a prestress strategy which delivers a compressive preload in this pattern. A banding of either high-strength tape or wire is wrapped around the pipe dipole assembly as shown in the figure. A piston, located on each side of the assembly, serves as a load concentrator. The capstan force delivered by the banding in any region is proportional to the arc angle subtended by the tape as it bends around the region. By shaping the pistons as shown, most of the arc angle (hence most of the compressive force) can be concentrated in the two side pistons and delivered to the dipole regions. We have done some preliminary finite-element modeling of the piston and the distribution of preload around the coil assembly. It appears to be feasible to match it fairly closely to the pattern of Lorentz stress.

Some experts have criticized this prestress strategy, on the basis that several prototype $\cos \theta$ dipoles were fabricated with wire-wrapped preload in the early phases of the Tevatron magnet R&D, and the magnets twisted uncontrollably after the assembly was released from the banding fixture. In our opinion, this result was predictable for the $\cos \theta$ geometry but irrelevant for the pipe geometry. In a $\cos \theta$ geometry, there is very little internal structure to the magnet. The structure is provided almost entirely by the collar assembly. Thus if one replaces the stack-weld lamination assembly by a wrap of banding, there is nothing to maintain alignment in a long magnet. By contrast, a pipe magnet has a massive internal structure, in the form of its magnetic and non-magnetic laminated cores (see Figure 4-3). This structure should provide excellent alignment integrity for a long magnet, independent of the means used to deliver preload. We note in closing that LBL has decided to use wire-wrap to deliver preload to the D-20 prototype, in which the steel shell can provide alignment integrity.

Figure 4-31. Short-sample measurements of j_c vs. B for Nb_3Al tape conductor.

Figure 4-32. Measurement of j_c vs. B in BSCCO tape.

Figure 4-33. Dependence of j_c on the angle between B and the tape-normal direction.

Figure 4-28. Distribution of Lorentz stress in the coil assembly of a 13 Tesla pipe dipole. Peak stress is 100 MPa.

D. Block-Coil Quadrupole for Low- β Insertions

One of the most challenging magnet design requirements for CERN's LHC is the low- β insertion at which the beams collide at high luminosity for each experiment. Attaining high luminosity requires that the beams be squeezed to the smallest feasible focus. Taylor³⁸ has designed an inner quadrupole triplet insertion which would produce $\beta^* = 0.5$ m at the intersect. The design is shown in Figure 4-29. It requires quadrupoles with an aperture of 70 mm and a gradient of 250 T/m. Design efforts have been undertaken at CERN, Fermilab, and LBL to design cos 2θ quadrupoles which would meet this requirement. It is at the limit of feasibility with NbTi, even at 2 °K. Such designs are problematic for two reasons. First, the inner quads will receive a heavy load of energy deposition from lost particles; the heat must be conducted through the coil, creating a temperature differential which would be especially problematic at 2° K. Second, most such designs have to push the SC/Cu ratio in the cable to problematic limits; the current density j_{Ca} which would appear in the Cu stabilizer is $\sim 1,300$ A/mm² in several such designs, beyond the capability of readily achievable quench protection strategies.

We have applied the same block-coil approach to design a block-coil quadrupole, using Nb₃Sn superconductor at 4.2 °K. It produces 300 T/m gradient (90% short sample), with an circular aperture of 70 mm. Figure 4-30 shows the calculated fields in the magnet. The block coil is oriented appropriately for relatively simple winding strategy. The cables are face-on to the direction of preload, providing a stiff modulus. The side boundaries of each coil segment are appropriate for mounting of a heater strip in excellent edge contact to all turns of the coil, assuring optimum rapid distribution of a quench using pulsed heaters. The 4.2 °K operation provides some margin for heat transport for beam losses; indeed the $j_c(T)$ for Nb₃Sn decreases more slowly with temperature than it does for NbTi.

With the block-coil approach, it is straightforward to design an asymmetric quadrupole. In the lattice of Figure 4-29, the beam envelope is asymmetric through the most critical elements (where the beam has largest size), $\beta_y \sim \beta_x/4$. The beam envelope is thus twice as wide as it is tall through the middle magnets of the triplet. We have designed a 2:1 asymmetric quadrupole to provide the highest feasible gradient in that region. Figure 4-12 shows the calculated fields. It provides 330 T/m gradient - 30% more than the LHC lattice requires. This design example illustrates again the power of the block-coil approach to design a buildable, optimal solution to a wide variety of magnet design requirements.

Figure 4-35. Low- β insertion for LHC. Note that $\beta_y \sim \beta_x/4$.

Figure 4-36. Symmetric block-coil quadrupole: 300 T/m gradient, 70 mm aperture, 4.2 °K.

E. Inorganic B-stage for Nb₃Sn Coil Insulation

In Nb₃Sn magnet technology, the strand or cable elements are wrapped with E-glass or S-glass cloth, either as a half-wrap or as a tubular sock. The coil is baked in a reaction bake cycle (~24 hour, 750 °C, inert atmosphere) to diffuse the Nb and Sn in the heterogeneous strand composition to form superconducting Nb₃Sn filaments. This process must be done after winding (wind-and-react) because the superconducting alloy is brittle and subject to fracture in winding and forming operations. The glass cloth cable insulation is typically impregnated with sizing (e.g. starch, ~2% by weight) to make it pliable for handling. The starch is burned out in an atmospheric bake to 400 °C prior to the reaction bake.

Immediately after the reaction bake, the coil is vacuum impregnated with an epoxy system; the impregnated coil is then cured to produce a solid composite. There are three good reasons for the vacuum impregnation. First, the glass cloth becomes extremely brittle after the sizing is burned out, and is prone to fracture. Second, the glass cloth can prevent cable-cable shorting, but cannot prevent electrical breakdown in He gas during a quench (the Paschen limit ~1,000 V). Intra-coil breakdown could damage the coil and its insulation. Third, the strands within a Rutherford cable must be supported by a matrix in the space between them, or the prestress forces would crush them at the points where strands pass over one another in the transposition pitch of the cable. At those locations the macroscopic preload would produce a stress concentration, which would yield the strand matrix and fragment the superconducting filaments, degrading j_c . The impregnated epoxy provides support in the inter-strand space so that stress does not concentrate.

The impregnation of a coil brings with it an unfortunate problem. Liquid helium is excluded from the coil, and cooling can only be provided at the coil boundaries. For a thick coil, heat produced in the coil must transport through the rather poorly conducting epoxy/glass matrix to be removed. Even a modest heat load could produce a significant temperature differential within the coil. In a typical collider magnet, two major heat sources are intimately associated with the coil: synchrotron radiation is absorbed on the beam tube, and beam losses produce energy deposition directly in the coil. These heat sources become more of a problem as the collider energy increases. Inclusion of additional materials in the epoxy/glass impregnation usually only makes the problem even worse. For example, the CERN group tried using mica as an inter-coil insulation. The mica developed microscopic voids between the lamina of the crystal structure, which caused its thermal conductivity to decrease tenfold.

What is needed is an insulating system which provides a solid support matrix in the inter-strand spaces within a cable element, and forms a dielectric coating on all strand surfaces to block gas breakdown during quench, and stabilizes the glass cloth wrap, but provides an open porosity within which liquid helium can flow in the (thin) gaps between cables in the coil package.

We propose to develop such a system. Several authors have developed similar insulation strategies^{34,35} is illustrated in Figure 4-13:

- A fluid composite of ceramic and glass powders, resin, and volatile vehicle is used to impregnate the cable and possibly the E-glass tape as well. Each is dried to remove the volatile vehicle, and to cure the resin if necessary;
- The tape is half-lap wound onto the impregnated cable;
- The insulated cable is wound onto the coil forms to fabricate the coil package;
- The ends of the inner layers are flared as described above;
- The completed coil is fired to remove all organic resins and sizing, then baked to react the Nb₃Sn.

The glass-ceramic-resin material must satisfy a number of criteria in order to provide the necessary functions described above. The liquid material must be capable of penetrating the cable in a dip process to fill the interstices between strands. The dried and cured material must adhere to the strands, and provide a flexible, cohesive bond to prevent decabling when bending the inner coil ends. The glass-ceramic mix must wet to the surface of the strands during the reaction bake, must not diffuse into the strands to a degree which would poison the superconducting performance of the Nb₃Sn alloy, and must form a tough matrix of very hard modulus after the reaction bake is completed. The mix must bridge the spaces between strands sufficiently to eliminate stress concentrations under face-on cable loading. The mix must form a continuous, vitreous coating on the strands to provide electrical isolation from the liquid helium. The voids left following the burnout of the resin (~50% of the mix by volume) must form an open matrix which permits penetration of liquid helium throughout the coil package.

Two lines of development are pertinent to a technical solution to these multiple demands. First, Ceramphysics has developed several glass-ceramic formulations in which the ceramic component provides large heat capacity at liquid helium temperature and reasonable thermal conductivity. While the ceramic component does not sinter at the ~750 °C reaction temperature of the cable, several glasses were used which vitrify at that temperature and provide a continuous matrix which incorporates the ceramic powder and wets to the cable strands. It was found that wetting required that a layer of nickel be electroplated on the strand surface. Nickel poses a diffusion contamination for Nb₃Sn, however, so it is suggested that the chromium plating which is being done for the ITER project may serve the same function of promoting wetting of the glass while also providing a diffusion barrier against any poisoning of the strand by components of the ceramic-glass mix.

Second, Ferro has developed a product line for thick-film technology which uses resin resin filled with ceramic and glass powders to produce a stable film for electronic substrates. If a suitable mix of glass and ceramic powders could be formulated in their resin resin, the above combination of properties might be achievable.

The overall process that is desired is akin to the "B-stage" process of epoxy impregnation for NbTi superconducting magnets (which do not require a reaction bake), in which green epoxy is loaded into a tape, wrapped onto the cable, and the completed coil is reacted to cure the epoxy while leaving porosity for helium penetration. A third company, Composite Technology Development, has developed processes of this sort and has committed to collaborate with us to develop the inorganic B-stage. They have a well-equipped test lab and can test most mechanical, electrical, and thermal properties of interest.

In order to achieve success with the proposed insulation strategy, it may be necessary to employ two seemingly disparate concepts, either separately or in concert. One concept uses binders, capable of carrying high loading of inorganic fillers, that can be thermally decomposed with near-zero char formation. The other concept is to use "pre-ceramic" polymers that are capable of being thermally decomposed at temperatures $<175^{\circ}\text{C}$ to form amorphous inorganic compounds with useful dielectric insulating properties.

With either concept it will be necessary to control the removal/decomposition of the resin carefully to assure that sufficient structural integrity, porosity, and coating of the individual cable strands are obtained. The important parameters to be controlled during thermal processing will include time, temperature, and the furnace atmosphere.

Low-char organic resins.

Two classes of low char forming resins will be considered: resins that decompose in air or oxygen-enriched atmosphere to give the typical volatile combustion products; and resins that will thermally degrade to form volatile organic products, usually the monomers from which the resins were originally made.

Resins susceptible to low temperature combustion.

Some candidate polymers to be considered as resin systems for the glass/ceramic insulation are listed below with comments:-

- Poly(vinyl alcohol), PVA, $[-\text{CH}_2-\text{CH}(\text{OH})-]_n$ - water soluble; capable of containing high loading of inorganic oxides; used to slip cast barium titanate ceramics.
- Poly(vinyl acetate), PVAC, $[-\text{CH}_2-\text{CH}(\text{OOCCH}_3)-]_n$ - probably capable of containing high loading of inorganic oxides.
- Poly(acrylic acid), PAA, $[-\text{CH}_2-\text{CH}(\text{COOH})-]_n$ - water soluble, very compatible with inorganic oxides, large technology base.
- Poly(ethylene oxide)/poly(ethylene glycol), PEO/PEG, $[-\text{CH}_2-\text{CH}_2-\text{O}-]_n$ - water soluble; forms complexes with metallate ions, compatible with inorganic fillers.
- Natural rubber latex emulsion (water) - very susceptible to oxidative degradation at relatively low temperatures, should be able to make suspensions with fine inorganic oxide powders and appropriate surfactants and dispersing agents.
- Poly(isobutylene), $[-\text{CH}(\text{CH}_3)_2-\text{CH}_2-]_n$ - low char forming polymer.
- Dow Chemical XUS-40303.00 high burn out binder, undisclosed composition; water and organic solvent soluble; used for ceramic fabrication as a "green" binder.

PVA, PVAC, PAA, and PEG all contain a high oxygen content ($C/O = 2/1$) to promote complete combustion under oxidizing conditions. This should facilitate the removal of the resin during burnout in air at elevated temperatures. For example, Union Carbide's Carbowax® PEG 20M is reported to leave an ash of only 0.05% theoretical during thermogravimetric analysis (TGA) in air to 375-400 °C. Because they are all polar polymers, they are compatible with inorganic compounds and should be able to handle high loading of filler compounds and still remain feasible.

The use of an elastomeric binder such as a natural rubber latex (in emulsion form for easy impregnation) or poly(isobutylene) which remains a liquid at room temperature when the formula weight is between 300 and 3,000 is potentially beneficial because it could lead to a more ductile cable assembly prior to burnout. The complete degradation of latex rubber is promoted by ozonolysis which promotes the breaking of C-C bonds. Thus it may be advantageous to use an ozone containing air atmosphere to facilitate the low temperature removal of elastomeric resins.

Dow Chemical's high-burnout binder, XUS-40303.00 is of interest, since it is designed to be used as a "fugitive" binder in the first stage preparation of monolithic ceramic shapes. It reportedly melts at 110-120 °C and undergoes a catastrophic decomposition at temperatures of 350-750 °C with a 99% weight loss.

Resins that pyrolyze with little or no char formation.

A number of readily available polymers thermally decompose essentially completely into volatile decomposition products. Most of these decompose by unzipping of the polymer chains to regenerate the volatile monomers. Some potentially useful pyrolyzing polymers are:

- n Poly(methylmethacrylate), PMMA, $[-CH_2-C(CH_3)(COOCH_3)-]_n$
- n Poly(alpha-methyl styrene), PMS, $[-CH_2-C(CH_3)(C_6H_5)-]_n$. These two polymers unzip completely at elevated temperatures in inert atmospheres with 100% regeneration of the volatile monomers.
- n Nylon 66 (polyamide) is interesting because it yields no char when it is combusted in air. Since one would expect at least moderate amounts of char from aerial thermolysis of a polyamide polymer, it likely at least unzips in part.
- Poly(dimethylsiloxane), PDMS, $[-Si(CH_3)_2-O-]_n$ polymers are commercially available with a wide range of molecular weights. They can be cured at 100-150 °C using conventional peroxide curing agents, and decompose at 600-700 °C without the formation of char. If the decomposition were carried out in air, we anticipate that a significant residue of amorphous silica would remain. A commercial copolymer of PDMS and methylmethacrylate is also available. This material also is expected to be a zero or near zero char former during thermal decomposition.
- Polycarbosilane polymers are being used as pre-ceramic polymers. Dietmar Seyferth, in an overview paper reports that polysilmethylene, $[-(CH_3)_2-Si-CH_2-]_n$, decomposes thermally in an inert atmosphere without the formation of char³⁹. W.P. Weber *et al.*

report two complex polycarbosilanes^{40,41} that when pyrolyzed in nitrogen between 550-750 °C and >450 °C respectively.

Pre-ceramic polymer resins.

Because of the current technical and industrial interest in both electronic and structural ceramic materials, a new technology has developed around the use of pre-ceramic polymers. These are polymeric materials that can be decomposed thermally under moderate to high temperatures to generate useful refractory ceramic materials. In contrast to fugitive (green) binders, when pre-ceramic polymers decompose they are converted in significant part into useful oxide or non-oxide ceramic materials. Much of the technology reported in the open chemical literature and the patent literature deals with the formation of the following crystalline phases:

- SiO₂;
- Al₂O₃;
- aluminosilicates;
- metal titanates;
- SiC;
- B₄C;
- TiB₂;
- Si₃N₄;
- refractory metal borides, carbides, nitride, and silicides.

Generally the thermal decomposition of the pre-ceramic polymers takes place in two steps. First the polymers are heated at moderate temperatures (<1,000 °C) to decompose the polymer and remove most of the volatile decomposition products and form amorphous ceramic precursor powders. Second the amorphous first stage decomposition products are annealed at sufficiently high temperatures to form the desired crystalline ceramic phases.

We plan to consider a number of pre-ceramic polymers as resins for impregnating the cable segments and the E-glass tape. One objective will be to generate amorphous oxide or non-oxide phases that will provide a structurally intact framework, useful porosity, and satisfactory dielectric properties.

As mentioned earlier, the exact stoichiometry of the amorphous chars, and the conversion efficiencies will depend on time, temperature, and the furnace atmosphere. By decomposing certain pre-ceramic polymers in air or under low partial pressures of oxygen it will be possible to form relatively low melting oxide glasses in relatively high yields. And, of course, it is possible to form glass/ceramic compositions that will form a liquid phase, below 750 °C, especially if certain inorganic glass forming modifiers are dispersed in the impregnating resins. Potential classes of pre-ceramic polymers are:

- Polycarbosilanes
- Polycarbosilazanes

- Silicone resins
- Filled high yield carbon precursor resins

A large number of polycarbosilane and polysilazane polymers have been commercially developed as precursors to SiC and/or Si₃N₄. For most of these polymers pyrolysis and high temperature annealing in ammonia promotes the formation of the nitride at the expense of the oxide. Some of these ceramic precursor polymers will be considered as resins for the glass/ceramic insulation system.

The silicone resins (rubbers) are an attractive potential class of polymer precursors to silica if they are thermally degraded in air or oxygen rich atmospheres. By loading them with boron and /or other metal compounds the silicone resins are potential precursor polymers for silicate, borosilicate, and aluminosilicate glasses or glass ceramics.

Although there are a number of commercial manufacturers of silicone resins, a particularly attractive one is RTV 161, available from General Electric. This resin uses a non-corrosive alkoxy cure system, and decomposes in air above 300 °C. RTV 560 is another attractive pourable silicone resin that decomposes in air above 260 °C. Such resins have been demonstrated as precursors to SiC when thermally decomposed in ammonia.

A series of U.S. Patents have been issued to Myers⁴². They disclose silazane and silazane polymer precursors to SiC and Si₃N₄. When fired in air at 1500 °C the best of these precursor polymers gave char yields > 90% based on Si. Of course much of this residual silicon was present as silicon oxides or silicon oxycarbides.

Liquid, thermosetting Si-O-C-N pre-ceramic polymers also are disclosed. They could be very attractive resins for the glass/ceramic insulation system.

Myers also developed a silazane modified phenolic resin that gave an 80% char yield based on Si and C. This pre-ceramic polymer was developed as a matrix resin for the manufacture of C/C composite materials.

Resins that give high char yields of carbon during pyrolysis in inert atmospheres also are of interest as matrix resins for the glass/ceramic insulation, especially when loaded with metals or metal precursor powders. In these cases inert atmosphere pyrolysis would generate char residues rich in refractory metal compounds.

F. Cost comparison between SSC dipoles and block dipoles

It is absurd in general to argue *pro* or *con* the manufacturing cost of a superconducting magnet before one has built and tested model magnets and even pre-production prototypes. However, it is appropriate to address here one particular criticism which has been made on several occasions concerning the potential for cost savings in pressing magnet technology to the high-field frontier: "The cost of a high-field magnet is mainly in its superconductor. As one pushes field strength ever higher, the total quantity of superconductor for a given energy storage ring grows, hence the cost grows, so the magnet system cost will grow with field strength."

We have attempted to address this criticism by comparing the major cost elements which comprise an SSC dipole, whose costs are now well documented, to the analogous costs for a 16 Tesla block-coil dual dipole. The SSC dipole cost was evaluated thoroughly during the final DOE review of the project. Figure 4-31 shows the evolution of the estimate of the cost per 16.5 m dipole, as various cost-saving potentials were evaluated. The resulting cost per magnet was ~\$160,000, divided roughly equally between finished parts (superconductor, beam tube, cryostat components, collar laminations, etc.) and labor for assembly.

To compare the block-coil dipole design to that of the SSC $\cos \theta$ dipole, we must compare conductor costs, the cost of parts other than conductor, and the labor for assembly. In consultation with Dr. McInturff, who is familiar with all aspects of the SSC dipole fabrication and with the fabrication issues for Nb_3Sn coils, we have endeavored to make a rough comparison of the two designs:

Conductor. *NbTi/Cu cable* costs ~\$100/lb in production quantity. The total conductor cost for an SSC dipole is \$40,000 (\$2,530/m).

Nb₃Sn/Cu cable costs ~\$300/lb in small-quantity today. There has never been a production-quantity application; suppliers estimate a quantity cost in the range \$150-200/lb. The range of total conductor cost for a block-coil dual dipole would be \$29,000-39,000/m.

Magnet Parts. *SSC dipole:* Deducting the above conductor cost from the \$80,000 component cost for an SSC dipole, the cost of all other finished parts is ~\$40,000 (\$2,310/m).

Block-coil dipole: The number and size of finished parts (e.g. lamination pieces, beam tubes, He shells, end fittings for one block-coil dual dipole is roughly twice that for one SSC dipole.

Magnet labor. *SSC dipole:* The labor cost for all assembly processes (coil winding; beam tube assembly; coil assembly and ground plane installation; lamination stacking and welding; collar assembly, prestress, and welding; iron lamination stacking, welding, and assembly; outer shell assembly and welding) is ~\$80,000/magnet (\$4,840/m)

Block-coil dipole: The coil assemblies should be considerably simpler to build and position than those for a $\cos \theta$ dipole, but there are more of them. There is only one set of laminated collars, instead of the two sets (non-magnetic and magnetic) on a $\cos \theta$ dipole.

On the other hand the Nb₃Sn coil assembly must undergo a reaction bake. Unless our new concept for inorganic B-stage insulation is successful, it will have to be vacuum impregnated just like the cos θ dipoles. Overall we estimate that the labor for fabrication of one block-coil dual dipole is roughly twice that to fabricate one SSC dipole.

Table 3 presents a cost comparison of the overall cost of the dipole magnets for a $\sqrt{s} = 40$ TeV hadron collider, under the above assumptions. Two costs are estimated for the block-coil dipoles, corresponding to the low and high extremes of the conductor cost estimation. The range of costs for the block-coil case brackets that of the SSC dipoles: the magnet costs are likely to be comparable for given energy, given aperture, etc. For a 2.5-times higher field strength, the tunnel cost is proportionately cheaper, and the siting of an ultimate-energy collider is proportionately easier.

There is one additional, more subtle potential for further substantial cost savings. The block-coil design which is shown in Figure 4-4 and used in calculating the costs in Table 3 is designed to provide an aperture of 5 cm. As discussed above, both the physical aperture and the good-field aperture of the magnet are likely more than is required for an ultimate-energy, ultimate-field collider. The aperture of the SSC dipoles, which received a tremendous amount of attention during 1992, was increased to 5 cm primarily because the field quality and injection sextupole fields were marginal for collider requirements with the original 4 cm aperture. The field calculations to date indicate that both concerns may be in fact quite acceptable with a block-coil design. The quantity of superconductor in the block-coil design scales as the square of the aperture. Reducing from a 5 cm to a 4 cm bore would reduce superconductor cost by 36%, total magnet cost by 30%.

The original criticism regarding the cost of higher field is simply based upon a false assumption: the superconducting cable represents only ~25% of the cost of an SSC magnet. There is real potential for cost savings and project enhancement by pressing the high-field frontier. Whether the potential is real or not can only be found from the proposed R&D program.

MATERIAL COST MATRIX GRAPH

AVERAGE RECURRING COST PER MAGNET

(CCB CHANGES ONLY)

Figure 4-37. Cost analysis of the SSC dipoles, from final DOE review.

Table 3. Cost comparison of SSC dipole and block-coil dipole

Cost element	SSC dipole	Block dual dipole		
cable conductor	NbTi/Cu	Nb3Sn/Cu		
cable cost	100	(low) 150	(high) 200	\$/m
central field	6.50	16	16	Tesla
amp-turns/beam	1	5	5	MA turns
superconductor cable area	1,440	11,000	11,000	mm**2
sc area/field strength/beam	222	344	344	mm**2/Tesla
magnet cable cost	2,530	29,040	38,720	\$/m
magnet components cost	2,310	4,620	4,620	\$/m
magnet labor cost	4,840	9,680	9,680	\$/m
total magnet cost	9,680	43,340	53,020	\$/m
total magnet length	126,720	25,740	25,740	m
total magnet ring cost	1,227	1,116	1,365	million \$

Research Plan

We have formed a collaboration with the Superconducting Magnet Program at Lawrence Berkeley Laboratory for the coordinated development of high field collider magnets which extend beyond the bounds imposed by NbTi superconductor and $\cos \theta$ coil geometry. It will be the only such effort in the world, so far as we are aware. The task is an ambitious one: it took 20 years to fully mature the conductor and magnet fabrication technologies for the current state-of-the-art. The task is manifestly a long-term R&D project. It is however absolutely vital if we are to prepare a credible technology base for possible future hadron colliders to push the energy frontier for high energy research.

We have developed a research plan for the first three years of the program, and an allocation of tasks between LBL and Texas A&M. The plan and milestones are summarized below, with detail provided in the WBS project schedule.

The design and fabrication of all prototype dipoles will be carried out at Texas A&M. We are requesting from TNRLC the allocation of the short-magnet fabrication facilities at SSCL. These facilities would give us an excellent basis for all aspects of magnet design and fabrication.

We have also requested from TNRLC and DOE the allocation of a short-magnet test cryostat, a liquid helium refrigerator system, and an ASSI magnet test electronics system which would support the testing of the dipoles at Texas A&M. Because of the necessity to plan our program with an absolute minimum of manpower, we plan to focus our hardware efforts during the first year entirely on commissioning the fabrication facilities and building the first two model magnets. LBL has agreed to test our first several magnets in their test cryostat. We plan to commission the refrigerator and the test electronics system during the second year, so that by the end of the second year we will be able to test magnets in-house.

LBL has agreed to supply us with all superconducting cable as required for our short model magnets. Their role in that respect is a tremendous boost, because they are among the most knowledgeable and best equipped group in the world for cabling and testing Nb₃Sn cable. LBL also plans to work with GE in developing and evaluating high-field Nb₃Sn tape, utilizing GE's tape process facility. If successful that effort would yield tape suitable for use in the pipe dipole PST-1 in the third year.

A summary list of the equipment which we are requesting from each of TNRLC and DOE follows the budget.

Year 1 Research Plan and Milestones

0. 13 Tesla $\cos \theta$ dipole tests (D20)

The D20 magnet should be completed in late 1993. Instrumentation for its testing is being built at the same time. Testing will commence in early 1994. One Texas A&M graduate student will come to LBL for ~6 months to participate in the testing (LBL support).

Milestone: Test results to be presented and reviewed at the Erice High-Field Magnet Workshop, May 1995.

1. NbTi block-coil dual dipole (BT-1)

The BT-1 magnet is a block-coil dual dipole, using NbTi cable. Its geometry, coil dimensions, and construction approach will be taken exactly from that of the 16 Tesla Nb₃Sn design. The purpose of BT-1 is to validate the field design, and to evaluate many practical issues of magnet fabrication: conductor placement tolerance, coil end strategy, preload strategy, and quench behavior. We may elect to use a B-stage epoxy insulation rather than vacuum impregnation, in order to evaluate some of the issues that will arise for the "inorganic B-stage" we plan to develop for use with Nb₃Sn coils. Because this magnet will be used for so many learning curves, it will be designed to be demountable so that we can try various coil, insulation, and preload approaches.

Milestone: Magnet tests in August 1995.

2. Insulation development

We plan to evaluate various options for a resin/glass/ceramic "B-stage" insulation scheme. Most tests will be conducted on small coil samples, to evaluate cure cycles, mechanical and electrical properties after reaction bake, and helium percolation. Once practical processes are developed, test coils will be built and tested in a steel flux shunt.

Milestone: Insulation development report to May 1995 review.

3. Nb₃Sn block-coil dual dipole (BS-1)

The BS-1 magnet will be our first prototype of the block-coil magnet with Nb₃Sn conductor. We will adapt the design and fabrication processes according to what we learn from BT-1. Issues of particular importance for this first model are evaluation of winding, reaction, insulation, and preload strategies. The coil will be instrumented with LBL strain gages throughout the coil assembly to measure the distribution of preload and Lorentz stress during cooldown, as a function of field strength, and during quench.

Milestone: Magnet testing in May 1996.

4. NbTi pipe magnet (PT-1)

PT-1 is another "learning magnet". We will use NbTi conductor in order to validate the field design, develop procedures for coil winding and assembly, and evaluate options for preload strategy. As with BT-1, all dimensions and design details will be taken directly from the Nb₃Sn design, so that we can evaluate the design and fabrication issues. Like BT-1, it will be designed to be demountable so that many tests can be made. One issue will perform be different, however: PT-1 will use NbTi cable, while the follow-on Nb₃Sn version may use tape conductor.

Milestone: Magnet testing in July 1996.

Project:
Date: 10/27/94

Critical Noncritical

Progress Milestone

Summary Rolled Up

WBS	Name	Qtr 4, 1994				Qtr 1, 1995				Qtr 2, 1995				Qtr 3, 1995				Qtr 4, 1995				Qtr 1, 1996				Qtr 2, 1996				Qtr 3, 1996								
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug		
1.4	Cryogenic design																																					
1.4.1	Cold mass design																																					
1.4.2	He circuit design																																					
1.4.3	Cooldown strategy																																					
1.4.4	Quench-mode vapor transport																																					
1.4.5	Cryogenic design review																																					
1.5	Fabrication development																																					
1.5.1	NbTi cable																																					
1.5.1.1	Conductor																																					
1.5.1.2	Cabling and insulation																																					
1.5.2	Coil winding prototypes																																					
1.5.2.1	Winding fixtures																																					
1.5.2.2	End supports																																					
1.5.2.3	Winding																																					
1.5.3	Test practice coils																																					
1.5.4	Lamination structures																																					
1.5.4.1	Laminations																																					
1.5.4.2	Stacking fixture																																					
1.6	Design review																																					
1.7	Design revisions																																					
1.8	Magnet fabrication																																					
1.8.1	Lamination structures																																					
1.8.1.1	Stack & weld blocks																																					
1.8.1.2	Assemble cores																																					
1.8.1.2	Coil cores																																					
1.8.1.2	Steel cores																																					

Critical Summary
 Noncritical Milestone Rolled Up

Project:
 Date: 10/27/94

Project:
Date: 10/27/94

Critical
Noncritical

Progress
Milestone

Summary
Rolled Up

Summary Rolled Up

Progress Milestone

Critical Noncritical

Project:
Date: 10/27/94

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
2.6.2.2	Cabling																							
2.6.2.3	Insulation																							
2.6.3	Lamination structures																							
2.6.3.1	Stamping die designs																							
2.6.3.2	Laminations																							
2.6.3.3	Stacking fixture																							
2.6.4	Coil winding prototypes																							
2.6.4.1	Winding fixtures																							
2.6.4.2	End supports																							
2.6.4.3	Reaction bake fixtures																							
2.6.4.4	Practice coils																							
2.6.4.4.	Winding																							
2.6.4.4.	Reaction bake																							
2.6.4.5	Test practice coils																							
2.6.5	Review at Ericc Magnet Workshop																							
2.6.6	Design revisions																							
2.7	Magnet fabrication																							
2.7.1	Lamination structures																							
2.7.1.1	Stack & weld blocks																							
2.7.1.2	Assemble cores																							
2.7.1.2.	Coil cores																							
2.7.1.2.	Steel cores																							
2.7.1.3	End supports																							
2.7.2	Coil winding																							
2.7.2.1	Coil 1(3 coils)																							
2.7.2.2	Coil 2 (3 coils)																							

Project:
Date: 10/27/94

Critical

Progress

Summary

Noncritical

Milestone

Rolled Up

WBS	Name	Qtr 4, 1994				Qtr 1, 1995				Qtr 2, 1995				Qtr 3, 1995				Qtr 4, 1995				Qtr 1, 1996				Qtr 2, 1996				Qtr 3, 1996							
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	
4.1.5	End coil design																																				
4.1.6	Review magnetic design																																				
4.2	Mechanical design																																				
4.2.1	Body coil stress analysis																																				
4.2.2	End coil stress analysis																																				
4.2.3	Coil winding strategy																																				
4.2.3.1	Dipole coil																																				
4.2.3.2	Toroid coil																																				
4.2.4	Coil insulation design																																				
4.2.5	Non-magnetic core design																																				
4.2.6	Magnetic core design																																				
4.2.7	Preload strategy																																				
4.2.7.1	Banding preload																																				
4.2.7.2	Interleaved lamination preload																																				
4.2.7.3	Gap w/aluminum spacer preload																																				
4.2.8	End coil support																																				
4.5.3.1	Stamping die designs																																				
4.2.9.1	Non-magnetic cores																																				
4.2.9.2	Magnetic core																																				
4.2.9.3	Interleaved collar																																				
4.2.10	Review mechanical design																																				
4.3	Electrical design																																				
4.3.1	Quench simulations																																				
4.3.2	Quench protection design																																				
4.3.3	Charging circuit design																																				
4.3.4	Review electrical design																																				

Project: Summary
Date: 10/27/94 Rolled Up

Critical Progress
Noncritical Milestone

Project: Date: 10/27/94	Critical Progress Summary Noncritical Milestone Rolled Up
----------------------------	---

WBS	Name	Qtr 4, 1994			Qtr 1, 1995			Qtr 2, 1995			Qtr 3, 1995			Qtr 4, 1995			Qtr 1, 1996			Qtr 2, 1996			Qtr 3, 1996	
		Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec	Jan	Feb	Mar	Apr	May	Jun	Jul	Aug
4.8	Magnet fabrication																							
4.8.1	Lamination structures																							
4.8.1.1	Stack & weld blocks																							
4.8.1.2	Assemble cores																							
4.8.1.2.	Coil cores																							
4.8.1.2.	Steel cores																							
4.8.2	Coil winding																							
4.8.2.1	Dipole coils																							
4.8.2.2	Toroid coils																							
4.8.3	Install instrumentation																							
4.8.4	Cold mass assembly																							
4.8.5	Prestress cold mass																							
4.9	Assemble magnet in cryostat																							
4.10	Magnet testing																							
4.11	Performance Review																							

Project:
Date: 10/27/94

Critical

Noncritical

Progress

Milestone

Summary

Rolled Up

Personnel (Gigatron)

Principal Investigator.

Peter M. McIntyre is a Professor of Physics at Texas A&M University. He has been devising new technology for accelerators for 15 years, including $p\bar{p}$ colliding beams, beam cooling experiments, gas microstrip chambers, superferric magnets for hadron colliders, and of course gigatron.

Physicists.

Jochen Trost is an Associate Research Scientist, who has been working on gigatron for the past three years.

Yaoqi Pang is a senior technologist with particular expertise in materials science and microfabrication techniques.

Students.

Bo Lee and Don Smith have both recently graduated after completing thesis research on the gigatron technologies.

Howard Demroff has experience with microwave techniques as well as clean-room fabrication technology.

Marcus Drew has built component elements of several of our fabrication instruments.

Technicians.

Tim Elliott is an electronic technician and also a CAD designer. He has wide expertise in the techniques and equipment we use to metalize and etch silicon.

Tapan Mazumdar is a technical physicist, with excellent hands-on ability to operate, tune, and repair our various elderly process fabrication equipment.

Personnel (High-Field Magnets)

The proposed project is an attempt to bring together a number of outstanding scientists, engineers, and technicians, half of whom are being laid off from the Super Collider, and a strong base of equipment from SSCL, to create a lean, mean team for design, building, and testing superconducting magnets. The team comprises all of the skills and experience necessary to assure an efficient, successful magnet R&D effort.

Principal Investigator.

Peter M. McIntyre is a Professor of Physics at Texas A&M University, and has a number of accelerator accomplishments to his credit: invention of $p\bar{p}$ colliding beams, beam cooling experiments at Fermilab, and development of the superferic design for collider magnets.

Physicists.

Sergio Pissanetzky is a Senior Scientist at the Houston Advanced Research Center. He has authored ~50 designs for advanced superconducting magnets, including the superferic collider magnets, a 4 Tesla whole-body MRI magnet, a high-current SMES test facility, and an open-geometry MRI magnet. Dr. Pissanetzky is author of MAGNUS, a 3-D Poisson code, and OPUS, a code which performs a constrained optimization of magnet design for multiple constraints and weighted performance criteria.

Charles Meitzler is a Professor of Physics at Sam Houston State University. He has ~15 years experience with linear accelerators and r.f. quadrupoles. During the past 5 years he has developed a state-of-the-art facility for precision measurement of high-field NMR spectroscopy magnets and of persistent-current joints for MR solenoids.

Gan Liang is a Professor of Physics at Sam Houston State University. He is a metallurgist, and has worked for the past 5 years on the development of improved techniques for insulating Nb₃Sn coils.

Weijun Shen is a pre-doctoral Research Assistant at Texas A&M University. He has conducted most of the calculations which are the basis of this proposal. He worked at SSCL for 2 years in magnet development, and built and tested several successful magnets there before joining Texas A&M two years ago.

Damir Latypov is a post-doctoral Research Associate at Texas A&M University. He has spent the past three years calculating quench propagation in a variety of magnets, and in making some of the most definitive measurements to date to experimentally validate quench simulations over a range of coil parameters.

Tarikh Jaffery has been a Scientist at SSCL. He has worked at both Fermilab and SSCL in testing the performance of the prototype magnets and the half-cell string at SSCL. He is familiar with all aspects of test design, hardware, and and procedure.

Engineers.

John Colvin is a senior cryogenic engineer at the Houston Advanced Research Center. He has ~20 years experience at Fermilab and at HARC in design, operation, and debugging of all forms of cryogenic equipment: refrigerators, compressors, cryocoolers, complex cryostats.

Richard Sims is a senior design engineer at SSCL. He has broad experience in project management, and in design and operation of most of the equipment which would be used to fabricate and test short model magnets.

Robert Wendt is a mechanical designer and engineer who has designed and built a wide variety of magnet fabrication equipment and cryostats. He worked at Fermilab for 15 years before joining SSCL.

Lucien Plesia is an electrical engineer with four years experience in control systems and data acquisition. He is the most knowledgeable expert on the hardware and software of the ASST test system.

Technicians.

Andrew Jaisle is a senior accelerator technician, with 10 years of experience at Brookhaven and SSCL in all aspects of superconducting magnet fabrication.

Mike Hentjes is a senior accelerator technician, with 15 years of experience at Fermilab and SSCL in building superconducting magnets, operating refrigerators, and conducting magnet measurements.

Richard Applegate is an accelerator technician with 5 years experience in assembling, commissioning, and operating the ASST system.

Tim Elliott is both an electronic technician and a CAD draftsman of excellent ability. He is expert in a wide range of vacuum techniques and in electronic equipment operation and repair.

¹H.M. Bizek *et al.*, IEEE Trans. Plasma Sci. 16, p.258 (1988);

²H.M. Bizek *et al.*, IEEE Trans. Electron Devices ED-36, p.2720 (1989).

³B. Lee *et al.*, "Knife-edge thin-film field emission cathodes", Proc. 1993 Particle Accelerator Conf., Washington, DC (1993).

⁴D.D. Smith *et al.*, "The oxidized porous silicon field emission array", Proc. 1993 Particle Accelerator Conf., Washington, DC (1993).

⁵C.A. Spindt *et al.*, J. Appl. Phys. 47, p.7089 (1976).

⁶C.A. Spindt *et al.*, "Field emission array development," Proc. 33rd Intl. Field Emission Symposium, Berlin, Germany, July 1986.

⁷W.K. Yue, "Electron Field Emission in Porous Silicon," Dissertation, Department of Electrical Engineering, Texas A&M University, August 1991 (unpublished).

⁸Bo Lee *et al.*, Appl. Surface Sci. 67, p.66 (1993).

⁹R.C. Jaklevic, L. Elie, W. Shen and J.T. Chen, Appl. Phys. Lett. 52, p.1656 (1988).

R.C. Jaklevic *et al.*, J. Vac. Sci. Technol. 86, p.448 (1988).

¹⁰A. Uhler, Bell System Technical Journal 35, 333 (1956).

¹¹V. Lehmann, J. Electrochem. Soc. 140, 2836 (1993).

¹²T. Unagami, J. Electrochem. Soc. 127, 476 (1980).

D.R. Turner, *Surface Chemistry of Metals and Semiconductors*, ed. H.C. Gatos, John Wiley & Sons, New York, 1960. pt III, p. 285.

Y. Arita, J. Crystal Growth 45, 383 (1978).

¹³R. Memming and G. Schwandt, Surface Sci. 13, 265 (1969).

¹⁴T. Unagami, J. Electrochem. Soc. 127, 476 (1980).

¹⁵R.C. Jaklevic *et al.*, J. Vac. Sci. Technol. A6, 448 (1988).

¹⁶M.I.J. Beale *et al.*, J. Crystal Growth 73, 622 (1985).

P. Searson *et al.*, J. Appl. Phys. 72, (1993).

Peter M. McIntyre

DATE OF BIRTH: September 26, 1947

EDUCATION: B.A. degree, Physics, University of Chicago, 1967
M.S. degree, Physics, University of Chicago, 1968
Ph.D. degree, Physics, University of Chicago, 1973

POSITIONS HELD:

1968--1969: Instructor, University of Chicago.
1972--1974: Research Associate, Enrico Fermi Institute.
1974--1975: Visiting Scientist, CERN.
1975--1979: Assistant Professor, Harvard University.
1979--1980: Group Leader, Internal Target Group, Fermilab.
1980--1986: Associate Professor, Texas A & M University.
1984--1991: Spokesman, Texas Accelerator Center.
1993--1994: Director, Texas Accelerator Center
1986--present: Professor, Texas A&M University.
1988--present: President, Accelerator Technology Corporation.
1990--1991: President, The American Physical Society, Texas Section.
1990--1991: Associate Dean, College of Science, Texas A&M University.
1990--1993: President, Board of Trustees, St. Michael's Academy,

AWARDS AND FELLOWSHIPS:

Sloan Foundation Fellow, 1980--82.
IR-100 Award, 1981: electron beam development and electron cooling experiment
Governor's Citation of Merit, 1989, leadership in the Texas siting of the SSC.

PATENTS:

CUTS: continuous unitized tunneling system.
Gigatron: a high efficiency microwave power source for linac colliders.
Structured coil design for superconducting magnets.
Pipe Magnet: compact dual dipole for hadron colliders.

Peter Mastin McIntyre

Peter Mastin McIntyre is a Professor of Physics at Texas A&M University. He studied at the University of Chicago, where he received his Ph.D. in 1973. He performed experiments with colliding beams at CERN in Geneva, Switzerland until 1975, then joined Harvard University as Assistant Professor. While there, he participated in neutrino scattering experiments at Fermilab. In 1976 he was the first to propose to make colliding beams of protons and antiprotons using the large synchrotrons at Fermilab and at CERN. This work led to the discovery of the weak bosons at CERN in 1982. He developed several techniques for cooling intense beams of antiprotons. In 1980 he was awarded an IR100 award for the invention of a new technique for high-efficiency collection of intense electron beams.

Since joining Texas A&M in 1980, he has conducted a search for magnetic monopoles in a nearby salt mine, and has participated in the construction and operation of the Collider Detector at Fermilab (CDF). Dr. McIntyre is an A.P.Sloan Foundation fellow, and is listed in *Who's Who in Science and Engineering*. Dr. McIntyre was among the first to propose the construction of the Superconducting Super Collider and was a co-author of the Texas SSC site proposal. In 1984, together with F.R. Huson, he founded the Texas Accelerator Center, a university-based laboratory for advanced accelerator research, and served as its Director in 1993-94. He has led the development of the relational database and curriculum development environment software for Project 2061, a national program for reform of K-12 science education. He is developing educational software for high energy physics and accelerator physics.

Dr. McIntyre is currently involved in three areas of research. He is participating in the CDF experiment at Fermilab, which is studying 2 TeV proton-antiproton collisions and has recently announced evidence for the top quark. He is developing new technology for future high-energy colliders: gigatron, a new high-power microwave amplifier for future e^+e^- linac colliders; a 16 Tesla dual dipole for future hadron colliders; and targetry and cooling for a 1 TeV $\mu^+\mu^-$ collider. He is developing the gas microstrip chamber, a new precision track chamber which offers excellent performance for high-energy collider experiments and also as an electronic X-ray camera for mammography.

Peter M. McIntyre

Publications

143. W boson + jet angular distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **73**, 2296 (1994).
142. Supersymmetry at a proposed $\sqrt{s} = 4$ TeV upgrade of the Fermilab Tevatron. (with T. Kamon, J.L. Lopez, and J.T. White), Phys. Rev. Lett. **50**, 5676 (1994).
143. Evidence for top quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D50**, 2966 (1994).
142. Evidence for top quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **73**, p. 225 (1994).
141. Measurement of the ratio $\sigma_B(W \rightarrow e\nu)/\sigma_B(Z^0 \rightarrow e^+e^-)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV (with F. Abe *et al.*), Phys. Rev. Lett. **73**, p. 220 (1994).
140. Measurement of the B^+ and B^0 meson lifetimes. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3456 (1994).
139. Measurement of the charged multiplicity of $Z^0 \rightarrow b\bar{b}$ events. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3145 (1994).
138. Search for excited quarks in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.3004 (1994).
137. Search for the top quark decaying to a charged Higgs boson in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **72**, p.1977 (1994).
136. Measurement of Drell-Yan electron and muon pair differential cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D49**, R1 (1994).
135. Search for first-generation leptoquarks in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV at CDF. (with F. Abe *et al.*), Phys. Rev. **D48**, p.R3939 (1993).
134. Prompt photon cross section measurement in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev **D48**, p. 2998 (1998).
133. Measurement of the dijet mass distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. **D 48**, p.998 (1993).

132. Study of porous silicon morphologies for electron transport. (with Y. Pang *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2711.
131. The oxidized porous silicon field emission array. (with D.D. Smith *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2708.
130. Knife-edge thin film field emission cathodes. (with B. Lee *et al.*), Proc. 1993 Particle Accelerator Conf., Washington, D.C., 17-20 May 1993. p. 2705.
129. Recent developments on gas microstrip chambers at Texas A&M. (with E.F. Barasch *et al.*), Proceedings of the 7th Meeting of the Am. Phys. Soc. Div. of Particles and Fields, 10-14 November 1992, Fermi National Accelerator Laboratory, Batavia, Illinois, vol.2, p.1782.
128. Gas microstrip detectors on polymer, silicon, and glass substrates. (with E.F. Barasch *et al.*), Nucl. Phys. B **32**, p.216 (1993).
127. Development of knife-edge field emission cathodes on (110) silicon wafers. (with Bo Lee *et al.*), Appl. Surface Sci. **67**, p.66 (1993).
126. Measurement of the average lifetime of B hadrons produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.3421 (1993).
125. Search for quark compositeness, axigluons and heavy particles using the dijet invariant mass spectrum observed in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.2542 (1993).
124. Inclusive χ_c and b-quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.2537 (1993).
123. Measurement of the bottom quark production in 1.8 TeV proton-antiproton collisions using muons from b-quark decays. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.2396 (1993).
122. Observation of $B_s^0 \rightarrow J/\psi \phi$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.1685 (1993).
121. Center-of-mass angular distribution of prompt photons produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.679 (1993).
120. Measurement of the bottom-quark production cross section using semileptonic decay electrons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **71**, p.500 (1993).

119. Study of four-jet events and evidence for double parton interactions in pp collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **47**, p.4857 (1993).
118. Measurement of the cross section for production of two isolated prompt photons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2232 (1993).
117. Measurement of jet multiplicity in W events produced in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.4042 (1993).
116. First measurement of the left-right cross-section asymmetry in Z boson production by pp collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2515 (1993).
115. Measurement of the cross section for production of two isolated prompt photons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.2232 (1993).
114. Search for $\Lambda_b \rightarrow J/\psi \Lambda$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **47**, p.R2639 (1993).
113. Comparison of jet production in $\bar{p}p$ collisions at $\sqrt{s} = 546$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.1376 (1993).
112. Measurement of jet shapes in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **70**, p.713 (1993).
111. The pipe magnet: compact 13 Tesla dual dipole for future hadron colliders. (with E. Badea and S. Pissanetzky), Proc. HEACC'92 Conference, Hamburg, Germany (1992).
110. Limits on the production of massive stable charged particles. (with F. Abe *et al.*), Phys. Rev. D **46**, R1889 (1992).
109. Inclusive $J/\psi(2S)$ and b-quark production in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.3704 (1992).
108. Dijet angular distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.2896 (1992).
107. Limit on the rare decay $W \rightarrow \gamma\pi$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p.2160 (1992).

106. RF breakdown and field emission measurement of SiO₂-coated copper electrodes. (with D. Sun *et al.*) Proc. 1992 Linear Accelerator Conf., August 24-28, 1992, Ottawa, Ontario, Canada, ed. C.R. Hoffmann, AECL-10782, vol. 2, p
105. Gated field-emitter cathodes for high-power microwave applications. (with E. Barasch *et al.*), Proc. 1992 Linear Accelerator Conf., August 24-28, 1992, Ottawa, Ontario, Canada, ed. C.R. Hoffmann, AECL-10782, vol. 2, p. 519.
104. Measurement of the production and muonic decay of W and Z bosons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **69**, p. 28 (1992).
103. Measurement of the B-meson and b-quark cross sections at $\sqrt{s} = 1.8$ TeV using the exclusive decay $B \rightarrow J/\psi K$. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 3403 (1992).
102. Measurement of the ratio $B(W \rightarrow \tau \nu) / B(W \rightarrow e \nu)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 3398 (1992).
101. Limit on the top-quark mass from proton-antiproton collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 3921 (1992).
100. Measurement of the isolated prompt photon cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 2734 (1992).
99. Gas microstrip chambers. (with E.F. Barasch *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch., **A315**, p. 170 (1992).
98. Properties of events with large total transverse energy produced in proton-antiproton collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 2249 (1992).
97. Search for new gauge bosons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1463 (1992).
96. Lepton asymmetry in W boson decays from $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1458 (1992).
95. Topology of three-jet events in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **45**, p. 1448 (1992).
94. Inclusive jet cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p. 1104 (1992).

93. Lower limit on the top-quark mass from events with two leptons in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **68**, p.447 (1992).
92. Measurement of $B^0 - \bar{B}^0$ mixing at the Fermilab Tevatron Collider. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.3351 (1991).
91. Measurement of the QCD jet broadening in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **44**, p.601 (1991).
90. Measurement of the Z boson p_t distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2937 (1991).
89. Search for $W^+ \rightarrow e^+ \nu$ and $W^- \rightarrow \mu^- \nu$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2609 (1991).
88. Measurement of the e^+e^- invariant-mass distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **67**, p.2418 (1991).
87. Measurement of $\sigma B(W \rightarrow e \nu)$ and $\sigma B(Z \rightarrow e^+ e^-)$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **44**, p.29 (1991).
86. Gated field-emission cathodes for microwave devices. (with H.P. Demroff *et al.*). Proc. IEEE Part. Acc. Conf., San Francisco, May 1991.
85. Measurement of the W boson p_t distribution in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **66**, p.2951 (1991).
84. The microstrip chamber: ultraprecise tracking for SSC detectors. (with E.F. Barasch *et al.*), Proc. Symp. on Detector Research and Development for the SSC, Fort Worth, Texas, p.209 (1990).
83. Measurement of the W boson mass. (with F. Abe *et al.*), Phys. Rev. Lett. **65**, p.2243 (1990).
82. Jet-fragmentation properties in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **65**, p.68 (1990).
81. Two-jet invariant-mass distribution at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. D **41**, p.1722 (1990).
80. Search for a light Higgs boson at the Fermilab Tevatron proton-antiproton collider. (with F. Abe *et al.*), Phys. Rev. D **41**, p.717 (1990).

79. Measurement of D^* production in jets from pp Collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.48 (1990).
78. Measurement of the ratio $W \rightarrow e\nu / Z \rightarrow ee$ in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.152 (1990).
77. Search for new heavy quarks in electron-muon events at the Fermilab Collider. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.147 (1990).
76. Pseudorapidity distributions of charged particles produced in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. D **41**, 2330 (1990).
75. Two-jet differential cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.57 (1990).
74. Search for the top quark in the reaction $\bar{p}p \rightarrow \text{electron} + \text{jets}$ at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **64**, p.142 (1990).
73. K_S^0 production in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. D **40**, p.3791 (1989).
72. Gigatron. (with H. Bizek *et al.*), IEEE Trans. on Electron Dev. **36**, p.2720 (1989).
71. Search for heavy stable charged particles in 1.8 TeV $\bar{p}p$ collisions at the Fermilab collider. (with F. Abe *et al.*), Phys. Rev. Lett. **63**, p.447 (1989).
- 70. The high field superferric magnet II. (with J.C. Colvin *et al.*), Particle Accelerators **30**, p.691 (1990).
69. Recent developments of gigatron technology. (with S.M. Elliott *et al.*), Particle Accelerators **30**, p.169 (1990).
68. Measurement of the mass and width of the Z^0 boson at the Fermilab Tevatron. (with F. Abe *et al.*), Phys. Rev. Lett. **63**, p.720 (1989).
67. Dijet angular distributions from $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.3020 (1989).
66. Limits on the masses of supersymmetric particles from 1.8 TeV $\bar{p}p$ collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.1825 (1989).
65. Advanced forward calorimetry for the SSC and Tevatron Collider.. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A279**, p.100 (1989).

64. Measurement of W boson production in 1.8 TeV $\bar{p}p$ collisions. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.1005 (1989).
63. Laboratory detector for solar axions. (with K. van Bibber, D.E. Morris, G.G. Raffelt), Phys. Rev. D **39**, p. (1989).
62. Measurement of the inclusive jet cross-section in $\bar{p}p$ collisions at $\sqrt{s} = 1.8$ TeV. (with F. Abe *et al.*), Phys. Rev. Lett. **62**, p.613 (1989).
61. Neutron-induced pulses in CDF forward hadron calorimeter. (with S. Cihangir *et al.*), IEEE Nucl. Sci. Symp. Orlando, Florida (1988).
60. Gigatron: a new technology for microwave power devices. (with S.M. Elliott *et al.*), Proc. SPIE Symp. on High Power Microwave Devices, Los Angeles (1988).
59. Gigatron. (with H.M. Bizek *et al.*), Proc. Workshop on Physics of Linear Colliders, Capri, Italy, p.377 (1988).
58. Transverse momentum distributions of charged particles produced in $\bar{p}p$ interactions at $\sqrt{s} = 630$ and 1800 GeV. (with F. Abe *et al.*), Phys. Rev. Lett. **61**, p.819 (1988).
57. A microwave power driver for linac colliders, Gigatron. (with H.M. Bizek *et al.*), Proc. Summer Study on High Energy Physics in the 1990's, Snowmass, CO, p.660 (1988).
56. The high-field superferric magnet. (with J.C. Colvin *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A270**, p.207 (1988).
55. Gigatron. (with H. Bizek, D. Raparia, and C. Swenson), IEEE Trans. Plasma Sci. **16**, p.58 (1988).
54. The CDF forward/backward hadron calorimeter. (with S. Cihangir *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **A267**, p.249 (1987).
53. The ribbon lasertron. (with D. Raparia and C. Swenson), Proc. 1987 IEEE Particle Accel. Conf., p.1688 (1987).
52. Multi-MeV accelerator system for ion implantation. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **B24/25**, p.83 (1987).
51. Multi-MeV ion implantation accelerator system. (with D. DiBitonto *et al.*), Nucl. Instr. and Meth. in Phys. Rsrch. **B21**, p.55 (1987).

50. Search for super-heavy GUT magnetic monopoles in cosmic rays. (with C. Gagliardi *et al.*), Phys. Rev. **D 35**, p.917 (1987).
49. The Collider Detector at Fermilab. (CDF) (with F. Abe *et al.*), IEEE Trans. Nucl. Sci. NS **33**, p.40. (1986).
48. A filter technique for shower shape discrimination, Forward Collider Physics Workshop. Fermilab, August 10, 1985.
47. The Texas Accelerator Center and the SSC, Proc. European Phys. Soc.; Bari, Italy. p.614, July, 1985.
46. Superferric magnet option for the SSC. (with H. Bingham *et al.*), IEEE Trans. Nucl. Sci. NS **32**, p.3462 (1985)
45. The three ring circus. (with D. Neuffer, W. Schmidt), IEEE Trans. Nucl. Sci. NS **32**, p.1704 (1985)
44. Superconducting Super Accelerator - challenge and opportunity. Proc. SSC Fixed Target Workshop, The Woodlands, Texas, January 26-30, p.1 (1984).
43. How to expose t quarks hidden in $\bar{p}p$ Collisions. (with M. Dechantsreiter, F. Halzen and D.M. Scott), Phys. Rev. **D 25**, p.258 (1982).
42. Searching for the GUT monopole, Proc. 1982 Workshop on Proton Decay Experiments, Argonne National Laboratory. ANL-HEP-PR-82-24, p.352 (1982).
41. Electron cooling for the Fermilab antiproton source. (with W. Kells, F. Krienen, F.E. Mills, L. Olekiuk and J. Peoples), IEEE Trans. Nucl. Sci. NS **28**, p.2583 (1981).
40. Electron cooling experiments at Fermilab. (with R. Forster *et al.*), IEEE Trans. Nucl. Sci. NS **28**, p.2386 (1981).
39. Nucleon structure functions from measurement of inelastic neutrino and antineutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. **D 23**, p.1045 (1981).
38. The forward spectrometer of the Fermilab Colliding Detector Facility, Proc. Madison Conf. on pp Collider Physics. AIP Conf. Proc. #85, p.263 (1981).
37. Very high energy antiproton physics: colliding 1 TeV "antiquarks" on heavy nuclei. (with F. Halzen), Phys. Rev. **D 21**, p.726 (1980).
36. The Fermilab High-Intensity Antiproton Source. Design Report. Fermilab (1979).

35. A filter technique for stochastic cooling of betatron oscillations. Fermilab TM-920 (1979).
34. The $\bar{p}p$ Program at Fermilab. Proc. XIVth Rencontre de Morionde, (Editions Frontiers, Paris) (1979).
33. Electron beam diagnostics in the Fermilab electron cooling experiment. (with W.P. Kells), IEEE Trans. Nucl. Sci. NS 26, p.3300.
32. The electron beam for the Fermilab electron cooling experiment (with W.B. Herrmannsfeldt *et al.*), IEEE Trans. Nucl. Sci. NS 26, p.3237.
31. Initial operation of the Fermilab antiproton cooling ring. (with D.B. Cline *et al.*), IEEE Trans. Nucl. Sci. NS 26, p.3158 (1979).
30. Measurement of the structure functions in neutrino and antineutrino inelastic interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, p.1317 (1979).
29. Rates and properties of trimuon events observed in high energy neutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, 1024 (1979).
28. Fast event recorder utilizing a CCD analog shift register. (with R.J. Ducar), Proc. 1978 IEEE Nucl. Sci. Symp., Washington, D.C., (1978).
27. Very high luminosity proton-antiproton storage rings. (with D.B. Cline, F.E. Mills and C. Rubbia), submitted to Phys. Rev. Lett., October, 1978.
26. Measurement of the energy and x dependence of the y distributions in antineutrino interactions. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 42, p.149 (1979).
25. Fermilab Electron Cooling Experiment Design Report. (with J. Bridges *et al.*) Fermilab (1978).
24. Rates and properties of opposite-sign dimuons from neutrinos and antineutrinos. (with A. Benvenuti *et al.*) Phys. Rev. Lett. 41, p.204 (1978).
23. Evidence for the production of prompt like-sign dimuon events by high-energy neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. 41, p.725 (1978).
22. ARGONAUT -- A novel detector for very high energy neutrino interactions. (with G. Harigel, H. Kautzky, and A. VanGinneken), Fermilab Proposal No.601D (1978).
21. Accommodating stochastic cooling at Fermilab. (with A. Ruggiero), Proc. Workshop on Producing High Luminosity, High Energy Proton-Antiproton Collisions, Lawrence Berkeley Laboratory (1978).

20. Further observation of trimuon production by neutrinos and antineutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **40**, p.8, p.488 (1978).
19. Limits of the probability that trimuons are produced by a new short-lived source of neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **40**, p.432 (1978).
18. Measurements of the proton-proton total cross-section and small-angle elastic scattering at ISR energies. (with L. Baksay *et al.*), Nucl. Phys. **B141**, p.1 (1978).
17. Characteristics of neutrino-produced dimuon and trimuon events as evidence for new physics at the lepton vertex. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **38**, p.1183 (1977).
16. Observation of a new process with trimuon production by high-energy neutrinos. (with A. Benvenuti *et al.*), Phys. Rev. Lett. **38**, p.1110 (1977).
15. Phase space cooling and $\bar{p}p$ colliding beams at Fermilab. (with E.R. Gray *et al.*), Proc. 1977 Part. Accel. Conf., p.1854 (1977).
14. Antiproton decay and the baryon number of the universe. (with D.B. Cline and C. Rubbia), Phys. Lett. **66B**, p.429 (1977).
13. How to observe the weak bosons in proton-antiproton collisions using existing accelerators. (with C. Rubbia and D. Cline), Proc. Int. Neutrino Conf., Aachen (Vieweg, Braunschweig), p.683 (1976).
12. Collecting antiprotons in the Fermilab Booster and very high energy $\bar{p}p$ interactions. (with D.B. Cline, F.E. Mills, C. Rubbia), Fermilab TM-689 (1976).
11. A new measurement of the K_S lifetime. (with S.H. Aronson *et al.*), Nuovo Cimento **32A**, p.236 (1976).
10. Evidence for double pomeron exchange at the CERN ISR. (with L. Baksay *et al.*), Phys. Lett. **61B**, p.89 (1976).
9. Experimental observation of copious yield of electrons with small transverse momenta in pp collisions at high energies. (with L. Baum, M.M. Block, B. Couchman, J. Crawford, A. Derevshchikov, D. DiBitonto, I. Golutvin, H. Hilscher, J. Ilion, A. Kernan, V. Kukhtin, J. Layter, W. Marsh, D. Schinzel, B. Shen, A. Staude, G. Tarnopolsky, R. Voss), Phys. Lett. **60B**, p.485 (1976).
8. Search for long-lived penetrating neutral particles. (with A. Benvenuti, D.B. Cline, W.T. Ford, R. Imlay, R.B. Jensen, T.Y. Ling, A.K. Mann, R. Orr, D.D. Reeder, J.

- Rich, C. Rubbia, R. Stefanski, L. Sulak, P.Wanderer), Phys. Rev. Lett. **35**, p.1486 (1975).
7. Precision experiments on muonium III: Ramsey resonance in zero field. (with D. Favart, D.Y. Stowell, V.L. Telegdi, R. DeVoe, and R. Swanson), Phys. Rev. **A8**, p.1195 (1973).
 6. A new precision measurement of the muonium hyperfine interval in argon. (with H.E.G. Kobrak, M. Eckhause, D. Favart, W.P. Kells, A. Magnon, J. Roehrig, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Phys. Lett. **B 43**, p.526 (1973).
 5. Muonium HFS splitting as a source of α . (with D. Favart, D.Y. Stowell, R.A. Swanson, V.L. Telegdi, and R. DeVoe). Proc. IVth Int. Conf. on Atomic Masses and Fundamental Constants, Teddington, England, September 6-10, 1971.
 4. Quadratic hfs pressure shifts of muonium in argon and krypton. (with D. Favart, D.Y. Stowell, V.L. Telegdi, R. DeVoe, and R.A. Swanson), Phys. Rev. Lett. **27**, p.1340 (1971).
 3. Precision measurement of the hyperfine interval of muonium by a novel technique: Ramsey resonance in zero field. (with D. Favart, D.Y. Stowell, R. DeVoe and V.L. Telegdi), Phys. Rev. Lett. **27**, p.1336 (1971).
 2. Measurement of the muon magnetic moment by "double resonance" in muonium, and a new value of α . (with R. DeVoe, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Proc. Int. Conf. on Precision Measurement and Fundamental Constants, Gaithersburg, MD, Aug. 3-7, (1970).
 1. Measurement of the muonium hfs splitting and of the muon moment by "double resonance", and a new value of α . (with R. DeVoe, A. Magnon, D.Y. Stowell, R.A. Swanson, and V.L. Telegdi), Phys. Rev. Lett. **25**, p.1779 (1970).