Title:

RELATIONSHIP BETWEEN HIGH-STRAIN-RATE
SUPERPLASTICITY AND INTERFACE MICROSTRUCTURE
IN ALUMINUM ALLOY COMPOSITES

Author(s):

J. Koike, Dept. of Mat. Sci., Tohoku Univ., Sendai 980-8579,
Japan
K.E. Sickafus, MST Div., LANL
T.E. Mitchell, CMS, LANL

RECEIVED
MAY 03 1999
OSTI

Submitted to:

Conference Proceeding "Microscopy - Microanalysis
Portland, Oregon, August 1st - 5th, 1999

Los Alamos
NATIONAL LABORATORY

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by the University of California for the U.S. Department of Energy under contract W-7405-ENG-36. By acceptance of this article, the publisher recognizes that the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. The Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

RELATIONSHIP BETWEEN HIGH-STRAIN-RATE SUPERPLASTICITY AND INTERFACE MICROSTRUCTURE IN ALUMINUM ALLOY COMPOSITES

J. Koike, K. E. Sickafus*, and T. E. Mitchell**

Dept. of Materials Science, Tohoku University, Sendai 980-8579, Japan

* Materials Science and Technology Division, Los Alamos National Laboratory

** Center for Materials Science, Los Alamos National Laboratory,
Los Alamos, NM 87535

The Al alloy composites reinforced with Si_3N_4 or SiC have been reported to exhibit superplasticity at high strain rate of faster than $1 \times 10^{-2} \text{ s}^{-1}$. It has been shown in many aluminum alloy composites that the optimum superplastic temperature coincides with an incipient melting temperature. The coincidence suggests a contribution of the liquid phase to the superplasticity mechanism. This paper shows a direct evidence of partial melting along matrix grain boundaries and matrix-reinforcement interfaces. Based on the obtained results, the role of the liquid phase in the high-strain-rate superplasticity is discussed.

The sample was Al-Mg (5052) alloy reinforced with 20vol% Si_3N_4 particles, fabricated by a powder metallurgy process. The sample showed an excellent superplasticity under the conditions given in Table 1. Partial melting was confirmed to occur at 821 K by differential scanning calorimetry. The microstructural changes during heating were observed in situ by TEM using a heating stage. The structure of interfaces and grain boundaries was observed by HREM. Chemical analysis was performed with EDS attached to VG-STEM.

A bright-field image of the composite is shown in Fig. 1. Notice that the edge of the Si_3N_4 particles are fragmented. Fig. 2 (a) shows a selected-area diffraction pattern taken at 821 K. A halo ring appears at this temperature, indicating partial melting. Fig. 2 (b) shows a dark-field image with an inverted contrast, taken from a part of the halo ring. The location of partial melting can be identified by a dark contrast along the matrix grain boundaries and the matrix-reinforcement interfaces. Above this temperature, grain-boundary corners become a rounded shape caused by the formation of the liquid phase at triple grain junctions. Figure 3 shows a concentration profile across a matrix-reinforcement interface. The left side is the aluminum matrix and the right is a Si_3N_4 particle. In the middle in between two dotted lines, there is a region where the Al and Si concentrations take intermediate flat values, indicating the formation of an interface phase. Mg segregation at the location of the left dotted line is also observed. This solute segregation is considered to be a cause for partial melting. The crystal structure of the interface phase was investigated by HREM and shown in Fig. 4. The figure shows the Al matrix and the interface phase. The interface is severely serrated and may become a stress concentration site during deformation. FFT of various regions reveals that the interface phase is composed of MgO , Al_2MgO_4 , and Mg_2Si .

In the present work, partial melting was observed along interfaces and grain boundaries. Solute segregation is suggested to be the cause for partial melting. The liquid phase is considered to act as a stress accommodation site that can prevent cavitation failure at the serrated interfaces and triple grain junctions.

This research was supported by the US DOE, OBES and by Japanese Ministry of Education.

Table. 1 Optimum conditions for high-strain-rate superplasticity.

elongation	temperature	strain rate	flow stress	strain rate sensitivity
700%	818±10 K	1 s ⁻¹	6 MPa	0.3

Fig. 1 BFI of the composite.

Fig. 2 (a) SAD and (b) DFI from the halo ring at 821 K with an inverted contrast.

Fig. 3 Concentration profile across the interface.

Fig. 4 HREM of the interface between the Al alloy matrix and the interface layer.