Performance of V-Cr-Ti Alloys in a Hydrogen Environment*

K. Natesan and W. K. Soppet
Energy Technology Division
Argonne National Laboratory
Argonne, IL 60439 USA

March 2000

The submitted manuscript has been created by the University of Chicago as Operator of Argonne National Laboratory ("Argonne") under Contract No. W-31-109-ENG-38 with the U.S. Department of Energy. The U.S. Government retains for itself, and others acting on its behalf, a paid-up, nonexclusive, irrevocable worldwide license in said article to reproduce, prepare derivative works, distribute copies to the public, and perform publicly and display publicly, by or on behalf of the Government.

RECEIVED
MAY 08 2000
OSTI

Presented at the 9th International Conference on Fusion Reactor Materials, Oct. 10-15, 1999, Colorado Springs, CO.

*Work supported by Office of Fusion Science, U.S. Department of Energy, under Contract W-31-109-Eng-38.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

PERFORMANCE OF V-Cr-Ti ALLOYS IN A HYDROGEN ENVIRONMENT

K. Natesan and W. K. Soppet

Energy Technology Division
Argonne National Laboratory
Argonne, IL 60439, U.S.A.

Abstract

A systematic study is underway at Argonne National Laboratory to evaluate the mechanical properties of several V-Cr-Ti alloys after exposure to environments containing hydrogen at various partial pressures. The goal is to correlate the chemistry of the exposure environment with hydrogen uptake by the samples and with the resulting influence on microstructures and tensile properties of the alloys. Other variables examined are specimen cooling rate and synergistic effects, if any, of oxygen and hydrogen on tensile behavior of the alloys.

Experiments were conducted to evaluate the effect of p_{H_2} in the range of 3×10^{-6} and 1 torr on tensile properties of two V-Cr-Ti alloys. Up to p_{H_2} of 0.05 torr, negligible effect of H was observed on either maximum engineering stress or uniform and total elongation. However, uniform and total elongation decreased substantially when the alloys were exposed at 500°C to 1.0 torr of H_2 pressure. Preliminary data from sequential exposures of the materials to low- p_{O_2} and several low- p_{H_2} environments did not reveal adverse effects on the maximum engineering stress or on uniform and total elongation when the alloy contained ≈ 2000 wppm O and 16 wppm H. Furthermore, tests in H_2 -exposed specimens, initially annealed at various temperatures, showed that grain-size variation by a factor of ≈ 2 had little or no effect on tensile properties. Also, specimen cooling rate had a small effect, if any, on the tensile properties of the alloy.

Key Words: Hydrogen and Hydrides, Embrittlement, Vanadium Alloys and Compounds, Mechanical Properties, Environmental Effects

1. Introduction

Vanadium-base alloys nominally containing 4-5 wt.% chromium and 4-5 wt.% titanium have been identified as the most viable materials for fusion reactor applications because they have lower long-term activation, lower irradiation afterheat, lower biological hazard potential and thermal stress factor, better creep resistance, compatibility with coolants such as liquid alkali

metals, and better mechanical formability than other structural alloys. A primary deterrent to the use of V-base alloys at elevated temperatures is their relatively high affinity for interstitial impurities, i.e., O, N, H, and C. The purpose of this study is to identify the key variables and establish performance envelopes for V-base alloys for service in H₂ environments. By analogy, the information can be used to assess the behavior of alloys in environments containing other H isotopes.

This paper examines the influence of H uptake of V-Cr-Ti alloys, specimen cooling rate, and grain size on the tensile properties of the alloys at room temperature [1-3]. Furthermore, the effects of simultaneous presence of O and H and their interactions on the tensile properties of the alloys are examined.

2. Experimental Procedure

The nominal compositions of the heats of V alloys selected for the study were V-4 wt.% Cr-4 wt.% Ti (identified as 44) and V-5 wt.% Cr-5 wt.% Ti (identified as 55). Chemical analyses of these heats are given in Table 1. The alloys were obtained as 1-mm-thick cold-rolled sheets. Samples with dimensions of about 1 x 10 x 20 mm were cut from each alloy. Before any further treatment or testing, all samples were annealed for 1 h at 1000°C in a vacuum of $\approx 10^{-6}$ torr. The samples were wrapped in Ti foil to protect them from contamination during annealing. Samples of Alloys 44 and 55 were exposed for 100 h at 200-500°C in pure H₂ gas environments with pressures in a range of 3×10^{-6} to 1 torr.

Furthermore, for a given pH₂ in the exposure environment, the H concentration in the V-base alloy increases as the temperature is lowered; this seems to indicate that the H concentration determined at room temperature will be influenced by the specimen cooling rate and that to obtain the value corresponding to that expected at the higher exposure temperature, fast cooling or quenching of the specimens may be needed. Experiments were conducted in which specimens were equilibrated at 350 or 500°C and cooled at a faster rate by pulling the specimens from the hot zone of the furnace into a flowing high-purity He atmosphere and using dry ice to cool the specimen. A cooling rate of 100 times that of normal rate is obtained by this approach.

Tensile specimens of several of the alloys were fabricated according to ASTM Standard E8-69 specifications and had a gauge length of ≈ 19 mm and a gauge width of ≈ 4.5 mm. Specimens were annealed for 1 h at 1000°C before H₂ exposure and tensile testing. Tensile specimens were exposed for 100-h exposure to environments containing H₂ at various partial pressures and at 200, 350, and 500°C. The H-exposed specimens were tensile-tested at a strain

rate of $1.8 \times 10^{-4} \text{ s}^{-1}$ at room temperature in air. Total elongation was measured with a vernier caliper and by using load/elongation chart records. The fracture surfaces and longitudinal and axial cross sections of tested specimens were examined by scanning electron microscopy (SEM). Several of the tested specimens were thinned in an acid solution and their microstructures were analyzed by transmission electron microscopy (TEM).

3. Results and Discussion

3.1. Hydrogen Uptake

Figure 1 shows the solubility of H in Ti and V as a function of temperature. It is evident that at a given temperature, the H concentration in Ti is much lower than in V for precipitation of their respective hydrides. However, because the Ti concentration in the V alloys of interest is in the range of 4-5 wt.%, $p\text{H}_2$ needed to precipitate TiH in the alloys will be much higher and probably closer to that for precipitation of VH. Furthermore, the H concentration in the alloy must exceed ≈ 100 wppm for VH to precipitate in the alloy at temperatures above $\approx 150^\circ\text{C}$. Exposure of specimens of Alloys 44 and 55 for 100 h at $200\text{-}500^\circ\text{C}$ in H environments with pressures of 3×10^{-6} to 1 torr yielded H concentrations in the specimens in a range of 6-360 wppm. Furthermore, a grain size increase by a factor of 2 (≈ 35 and $55 \mu\text{m}$ for large-grain specimens of Alloys 44 and 55 obtained by annealing at 1200°C , versus 18 and $30 \mu\text{m}$ in specimens of the same alloys annealed at 1000°C) did not have a significant effect on H uptake of the alloys.

3.2. Effect of Cooling Rate

As discussed earlier, cooling rates can have an effect on the H uptake of the alloys because the H concentration in the alloy increases as the temperature decreases at a given $p\text{H}_2$ in the environment. Therefore, H can transfer to the alloy, depending on the length of time the alloy is exposed to the higher $p\text{H}_2$ at lower temperatures. Figure 1 shows temperature-versus-time plots for normal cooling rate from 500°C and fast cooling rates from 500 and 350°C . The rates in the normal and fast cooling were ≈ 0.04 and 4.5°C/s and the total time to reach $\approx 50^\circ\text{C}$ in the fast cooling was < 100 s. Table 2 shows the tensile properties for Alloy 44 exposed at a nominal $p\text{H}_2$ of $\approx 10^{-6}$ torr at 500 and 350°C and cooled at various rates. Results indicate that the cooling rate has very little effect on the tensile properties of specimens exposed at 500°C . At 350°C , the fast-cooled specimen exhibited some decrease in maximum engineering stress and some increase in uniform and total elongation, compared with those for normal-cooled specimens.

3.3. Effect of H Concentration on Tensile Behavior

Figure 2 shows engineering stress/engineering strain plots at room temperature for Alloys 44 and 55 in as-annealed condition and after exposure at 500°C in pH_2 levels of 3×10^{-6} and 0.01 torr. Table 3 lists the tensile data obtained on Alloy 44 after exposure at various temperatures and H_2 pressures. Results showed that in the pH_2 range of this study, Alloy 44 exhibited a small decrease in uniform and total elongation after exposure to H_2 at 500°C. Furthermore, tensile test data generated at 200-500°C after exposure to pH_2 levels in the range of 1×10^{-6} - 5×10^{-2} torr showed little or no effect on the maximum engineering stress for Alloy 44. Figure 3 shows plots of uniform and total elongation values as a function of H concentration for the alloy exposed at 200, 350, and 500°C and tested at room temperature. Uniform and total elongation values for the alloy ranged between 0.14-0.20 and 0.18-0.31, respectively, at 200 and 500°C and in $pH_2 < 0.05$ torr. Only at a pH_2 of 1 torr and at 500°C did the uniform elongation for the alloy decrease to 0.002. This corresponded to an H concentration of ≈ 360 wppm in the alloy, indicating that this H level may be the threshold for embrittlement of the alloy. DiStefano et al., based on their studies, concluded that > 500 wppm H is needed for embrittlement of Alloy 44 [4].

To examine the effect of initial grain size on subsequent H uptake and tensile properties, specimens of Alloys 44 and 55 were annealed for 2 h at 1200°C, which increased the grain size of the alloys by at least a factor of 2 over those annealed for 1 h at 1000°C. With the increased grain size, both alloys exhibited some increase in strength and some decrease in elongation (see Table 4). Similar effects were observed when the specimens were exposed for 100 h at 500°C to a pH_2 of 3×10^{-6} torr.

3.4. Synergistic Effect of O and H on Tensile Properties

To examine the synergistic effect, if any, of O and H in the alloy on the tensile behavior of V-Cr-Ti alloys, specimens of the Alloys 44 and 55 were pretreated in several low- pO_2 environments for 100 h at 500°C. Subsequently, the exposure gas was changed from O_2 to H_2 at the same temperature, and specimen exposure was continued for another 100 h. Preexposure of the specimens to the low- pO_2 environments resulted in different concentrations of O in the alloys, which were subsequently exposed to various H_2 pressures. The specimens exposed to the dual treatment were analyzed for O and H by vacuum fusion. Table 5 lists the O and H concentrations for specimens with different treatments. The O concentrations ranged between 550 and 2230 wppm, while the H concentration range was 6-16 wppm. It should be noted that

the diffusion coefficient for O is a few orders of magnitude lower than that for H in these alloys; as a result, after the 100-h exposures, the measured H concentration will be uniformly distributed over the entire 1-mm-thick section of the specimens, while the O concentration will be confined to a depth of $\approx 50\text{ }\mu\text{m}$ from the surface [5,6].

The pretreated and H-exposed specimens were tensile-tested at a strain rate of $1.8 \times 10^{-4}\text{ s}^{-1}$ in room-temperature air. Engineering stress/engineering strain curves from various tests were analyzed to evaluate the effect of dual treatment on the tensile properties for the alloys. Table 6 shows the values for maximum engineering stress and uniform and total elongation for the two materials after the dual treatments. Figures 4 and 5 show the maximum engineering stress and the uniform and total elongation as a function of O concentration for both the alloys. It is evident that O concentration up to $\approx 2300\text{ wppm}$, even though confined to the surface regions of the specimens, has a negligible effect on tensile properties; no synergistic effect of O and H on the properties is observed when the H concentration in the alloy was in the range of 6-16 wppm, based on the present study. However, DiStefano et al. reported embrittlement of the alloy at room temperature after preoxidation at 500°C to obtain 800 wppm O and with subsequent H uptake of 100 wppm [4]. Results developed in both these studies indicate that the interaction between O and H in the V-base alloys may be more complex and needs significant additional effort to clarify whether a synergistic effect of O and H is present and to assess the magnitude of this effect on the mechanical properties of the alloys.

3.5. Microstructural Observations

Microstructures of specimens from various tensile tests without and with pretreatment of O were examined by TEM, and preliminary observations are reported below [6]. Alloy 44 specimen after exposure to pH_2 of $3 \times 10^{-6}\text{ torr}$ at 500°C contained 11 wppm H and exhibited clean grain boundaries with no hydride precipitates, as expected. Even with 35 wppm H in the specimen, alloy grain boundaries and grain interiors were devoid of precipitates, indicating no preferential segregation of H or hydrides in the specimen.

Alloy 44 specimen that was pretreated for 100 h in $3 \times 10^{-6}\text{ torr pO}_2$ at 500°C and subsequently exposed for 100 h in pH_2 of $3 \times 10^{-6}\text{ torr}$ at 500°C contained O, N, and H concentrations of 1030, 100, and 7 wppm, respectively. The specimen exhibited uniform and total elongation values of 0.15 and 0.23, respectively. TEM analysis showed precipitates predominantly along the grain boundaries, which can be attributed to the pretreatment in the low- pO_2 environment. Grain boundaries in the alloy exhibited precipitates of $\approx 100\text{-}200\text{ }\text{\AA}$ in size.

The Alloy 44 specimen that was pretreated for 100 h in 1×10^{-4} torr pO_2 at $500^\circ C$ was subsequently exposed for 100 h in pH_2 of 3×10^{-6} torr at $500^\circ C$ contained O, N, and H concentrations of 2020, 110, and 13 wppm, respectively. TEM analysis showed extensive continuous precipitation along the grain boundaries and some preferential precipitation within some grains but not in others. We plan to analyze the precipitates in these specimens and also to examine specimens from several other experiments to evaluate the effect of increased H concentration and O/H interactions on the microstructures and tensile properties of the alloy.

4. Summary

We have evaluated the effect of H uptake of Alloys 44 and 55 in pH_2 in the range of 3×10^{-6} to 1 torr on tensile properties of the alloys. The effect of pH_2 in the range of pH_2 of 3×10^{-6} to 5×10^{-2} torr on tensile properties is minimal; at a pH_2 of 1 torr, the maximum engineering stress is unaffected but the tensile elongation decreased significantly. The H concentration corresponding to this condition is ≈ 360 wppm. Effect of H on the tensile properties of Alloys 44 and 55 with enlarged (by a factor of 2) grain sizes was negligible. Preoxidation (resulting in an O concentration of ≈ 2000 wppm) and subsequent H_2 exposure (resulting in 16 wppm H) did not affect the tensile properties of the alloy at room temperature. TEM analysis of specimens exposed to low- pH_2 atmosphere exhibited neither segregation of H in the grain boundaries nor any precipitates of hydrides. Specimens with oxygen concentrations of 1030 and 2000 wppm (present due to low-pressure O_2 pretreatment) exhibited significant precipitation of, presumably, oxides along the grain boundaries and within some of the grains in the alloy.

Acknowledgments

This work supported by Office of Fusion Science, U.S. Department of Energy, under Contract W-31-109-Eng-38. D. L. Rink assisted with the H exposures, tensile tests, and microstructural analysis. E. Ryan assisted with TEM examination of tested specimens.

References

- [1]. K. Natesan and W. K. Soppet, "Tensile Properties of V-Cr-Ti Alloys after Exposure in Hydrogen-Containing Environments," Fusion Reactor Materials Progress Report for the Period Ending December 31, 1997, Argonne National Laboratory, DOE/ER-0313/23, p. 127, March 1998.
- [2]. K. Natesan and W. K. Soppet, "Tensile Properties of V-Cr-Ti Alloys after Exposure in Hydrogen-Containing Environments," Fusion Reactor Materials Progress Report for the Period Ending June 30, 1998, Argonne National Laboratory, DOE/ER-0313/24, p. 68, Sept.

1998.

- [3]. K. Natesan and W. K. Soppet, "Tensile Properties of V-Cr-Ti Alloys after Exposure in Hydrogen-Containing Environments," Fusion Reactor Materials Progress Report for the Period Ending December 31, 1998, Argonne National Laboratory, DOE/ER-0313/25, p. 21, April 1999.
- [4]. J. R. DiStefano, B. A. Pint, J. H. DeVan, H. D. Rohrig, and L. D. Chitwood, presented at 9th Int. Conference on Fusion Reactor Materials, Colorado Springs, CO, Oct. 10-15, 1999.
- [5]. K. Natesan and M. Uz, "Oxidation Kinetics and Microstructure of V(4-5)wt.% Cr-(4-5)wt.% Ti Alloys Exposed to Air at 300-650°C," Fusion Reactor Materials Progress Report for the Period Ending June 30, 1996, Argonne National Laboratory, DOE/ER-0313/20, p. 105, Oct. 1996.
- [6]. M. Uz, K. Natesan, and V. B. Hang, J. Nucl. Mater. 245 (1997) 191-200.

Table 1. Compositions of V-Cr-Ti alloys used in hydrogen studies

Alloy	Heat #	Composition					
		Cr (wt.%)	Ti (wt.%)	Si (wppm)	O (wppm)	N (wppm)	C (wppm)
44	832665	3.8	3.9	783	310	85	80
55	832394	4.6	5.1	310	440	28	73

Table 2. Effect of cooling rate on room temperature tensile properties of Alloy 44

Exposure temperature (°C)	pH ₂ (torr) in exposure environment	Cooling rate (°C/s)	Maximum engg. stress (MPa)	Uniform elongation	Total elongation
500	3 x 10 ⁻⁶	0.04	440	0.174	0.263
	1 x 10 ⁻⁶	4.5	433	0.164	0.301
350	1 x 10 ⁻⁶	0.04	434	0.133	0.184
	1 x 10 ⁻⁶	4.5	418	0.182	0.331

Table 5. Concentrations of O and H in pretreated tensile specimens^a

pO ₂ in exposure environment (torr)	pH ₂ in exposure environment (torr)	Concentration (wppm)			
		Oxygen		Hydrogen	
		55	44	55	44
-	3 x 10 ⁻⁶	550	670	12	11
3 x 10 ⁻⁷	1 x 10 ⁻⁶	625	620	16	16
1 x 10 ⁻⁶	1 x 10 ⁻⁶	730	1030	6	7
1 x 10 ⁻⁴	3 x 10 ⁻⁶	2230	2000	15	12

^aPreexposure in O₂ was 100 h at 500°C, and subsequent exposure in H₂ was 100 h at 500°C.

Table 6. Effects of dual O/H treatment^a at 500°C on room temperature tensile properties of V-Cr-Ti alloys

pO ₂ in exposure environment (torr)	pH ₂ in exposure environment (torr)	Maximum engg. stress (MPa)		Uniform elongation		Total elongation	
		55	44	55	44	55	44
		55	44	55	44	55	44
-	-	469	424	0.165	0.186	0.303	0.322
-	3 x 10 ⁻⁶	437	440	0.189	0.174	0.313	0.263
3 x 10 ⁻⁷	1 x 10 ⁻⁶	452	453	0.173	0.162	0.297	0.266
1 x 10 ⁻⁶	1 x 10 ⁻⁶	507	475	0.165	0.146	0.268	0.228
1 x 10 ⁻⁴	3 x 10 ⁻⁶	484	451	0.132	0.136	0.184	0.177

^aPreexposure in O₂ was 100 h at 500°C and subsequent exposure in H₂ was 100 h at 500°C.

Fig. 1. Temperature-time curves for normal and fast cooling of specimens from H₂ exposure temperature.

Fig. 2. Engineering stress/engineering strain plots for Alloys (a) 44 and (b) 55 in as-annealed condition and after 100-h exposure at 500°C to various pH_2 levels and normal cooling rate.

Fig. 3. (a) Uniform and (b) total elongation as a function of H concentration for V-4Cr-4Ti alloy tested at room temperature

Fig. 4. Maximum engineering stress as a function of O uptake during preoxidation and subsequent H_2 exposure for Alloys 44 and 55 tested at room temperature.

Fig. 5. Uniform and total elongation as a function of O uptake during preoxidation and subsequent H_2 exposure for Alloys 44 and 55 tested at room temperature.