**OAK RIDGE
NATIONAL
LABORATORY**

Potential Effects of Gallium on Cladding Materials

**Dane F. Wilson
Edward C. Beahm
Theodore M. Besmann
Jackson H. DeVan
James R. DiStefano
Uri Gat
Sherrell R. Greene
Phillip L. Rittenhouse
Brian A. Worley**

MANAGED AND OPERATED BY
LOCKHEED MARTIN ENERGY RESEARCH CORPORATION
FOR THE UNITED STATES
DEPARTMENT OF ENERGY

ORNL-27 (3-96)

JS **MASTER**
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

089

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P. O. Box 62, Oak Ridge, TN 37831; prices available from (423) 576-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Metals and Ceramics Division

Potential Effects of Gallium on Cladding Materials

Dane. F. Wilson
Edward C. Beahm
Theodore M. Besmann
Jackson H. DeVan
James R. DiStefano
Uri Gat
Sherrell R. Greene
Philip L. Rittenhouse
Brian A. Worley

Date Published: October 1997

NOTICE: This document contains information of a preliminary nature.
It is subject to revision or correction and therefore does not represent a final report.

Prepared for the
U.S. Department of Energy
Office of Fissile Materials Disposition
GA 01 02 01 4

Prepared by the
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
LOCKHEED MARTIN ENERGY RESEARCH
for the
U.S. DEPARTMENT OF ENERGY
under contract DE-AC05-96OR22464

CONTENTS

LIST OF TABLES	iv
ACRONYMS	v
EXECUTIVE SUMMARY	vi
1. INTRODUCTION	1
2. GALLIUM IN WG MOX FUEL	2
2.1 AS-FABRICATED WG MOX FUEL	2
2.2 CHEMISTRY	2
2.2.1 Agglomerates	2
2.2.1.1 Oxidation potential	2
2.2.2 Bulk Fuel Chemistry	9
2.2.2.1 Oxide formation	9
2.2.3 Reactions with Fission Products	10
2.3 GALLIUM TRANSPORT MECHANISMS WITHIN FUEL	10
2.3.1 Gas Phase Transport	10
2.3.2 Solid-State Transport	12
3. CLAD PERFORMANCE AND DEGRADATION MECHANISMS	15
3.1 INTRODUCTION	15
3.2 FUEL-SIDE CORROSION	17
3.2.1 Environment/Burnup	17
3.2.2 Material Variables	18
3.2.3 Pellet Clad Interaction	19
3.2.4 Mechanisms of Gallium Embrittlement	19
3.3. WATERSIDE CORROSION	21
4. GALLIUM AND FUEL PERFORMANCE: CONCLUSIONS AND RECOMMENDATIONS	23
REFERENCES	26
APPENDIX	
PHYSICAL, CHEMICAL AND NUCLEAR CHARACTERISTICS OF GALLIUM AND GALLIUM OXIDES	A-1
A.1 ELEMENTAL GALLIUM	A-1
A.1.1 PHYSICAL CHARACTERISTICS	A-1
A.1.2 CHEMICAL CHARACTERISTICS	A-2
A.1.3 NUCLEAR CHARACTERISTICS OF GALLIUM	A-3
A.2 GALLIUM OXIDES	A-5
A.3 IMPURITIES	A-5
A.3.1 HALOGEN IMPURITIES	A-5
A.3.2 CHALCOGENIDE IMPURITIES	A-6
A.3.3 REACTIONS WITH GROUP V ELEMENTS	A-6
A.4 REFERENCES	A-7

LIST OF TABLES

Table 1. Fission product concentrations computed for a burnup of 52.5 MWd/kg and their oxidation state assuming gallium is present as the oxide in as-fabricated fuel	6
Table 2. Fission product concentrations computed for a burnup of 52.5 MWd/kg and their oxidation state assuming gallium is present unoxidized in as-fabricated fuel	7
Table 3. Thermodynamic values at 1000 K for the gallium-oxygen system	11
Table A.1. Physical properties of gallium	A-1
Table A.2. Gallium compounds with zirconium or plutonium	A-2
Table A.3. Chemical properties of gallium	A-3

ACRONYMS

BWR	boiling-water reactor
HE	hydrogen embrittlement
ISCC	intergranular stress corrosion cracking
LANL	Los Alamos National Laboratory
LME	liquid metal embrittlement
LWR	light-water reactor
MOX	mixed oxide
O/M	oxygen-to-metal
PCI	pellet-clad interaction
PWR	pressurized-water reactor
R&D	research and development
SCC	stress corrosion cracking
SMIE	solid metal-induced embrittlement
WG	weapons grade

EXECUTIVE SUMMARY

The Department of Energy has announced that the United States will pursue a dual-track approach to the disposition of plutonium arising from the dismantling of nuclear weapons. The dual-track disposition approach involves both immobilization and reactor-based mixed oxide (MOX) fuel technologies. The use of the MOX fuel option requires the assessment of the potential impact of gallium (on the order of 10 ppm), not present in conventional MOX fuel, on cladding material performance.

This paper identifies and examines issues concerning the incorporation of gallium in weapons-derived plutonium in light water reactor (LWR) MOX fuels. Particular attention is given to the more likely effects of the gallium on the behavior of the cladding material. The chemistry of weapons-grade (WG) MOX, including possible consequences of gallium within plutonium agglomerates, was assessed. Based on the calculated oxidation potentials of MOX fuel, the effect that gallium may have on reactions involving fission products and possible impact on cladding performance were postulated. Gallium transport mechanisms are discussed. With an understanding of oxidation potentials and assumptions of mechanisms for gallium transport, possible effects of gallium on corrosion of cladding were evaluated. Potential and unresolved issues and suggested research and development (R&D) required to provide missing information are presented.

This analysis concludes that without control of the stoichiometry of the MOX fuel it is possible for the gallium to be present as either elemental gallium or gallium sesquioxide (Ga_2O_3) in the as-fabricated fuel. To keep gallium as a metal oxide in the as-fabricated fuel, the fuel oxygen-to-metal ratio (O/M) should be at least equal to 2. During burnup, in an isolated plutonia aggregate the fission products molybdenum, technetium, cadmium, tin, antimony, tellurium, and some ruthenium are computed to be present as oxides.

At temperatures approaching >1200 K, the vapor pressure of gaseous gallium oxide (Ga_2O) will be of the order of 10^4 to 10^5 Pa. Within the fuel rod, the oxide species may vaporize in significant quantities in the hotter regions and transport to the cooler clad surfaces, where it would condense. Should this mode of mass transfer be particularly effective, reduction of the Ga_2O_3 by the zirconium in the clad could have detrimental effects on clad performance. However, significant burnup could serve to reduce this mode of mass transport.

General corrosion of the cladding with gallium or gallium oxide is not a concern. General corrosion is mass limited, and the mass of gallium present in the fuel volume is low relative to the clad volume. However, localized corrosion (grain boundary penetration) and

liquid-metal embrittlement by gallium are possible compatibility issues that need further investigation. The possibility that gallium will influence water (aqueous) corrosion is considered remote.

1. INTRODUCTION

The Department of Energy announced in January 1997 that the United States will pursue a dual-track surplus plutonium disposition approach in which both immobilization and reactor-based mixed oxide (MOX) fuel technologies will be employed.

Currently, more than a dozen commercial light-water reactors (LWRs) in Europe use recycled plutonium in MOX fuel assemblies. More than 300,000 LWR MOX fuel rods have been irradiated during the past decade. The performance of this commercial LWR MOX fuel has proven to be satisfactory. However, the U.S. weapons-grade (WG) plutonium differs from the commercial recycled reactor-grade plutonium used in Europe in that the WG plutonium contains small quantities (up to 1 mass %) of gallium, an active material that readily reacts with most metallic materials. Processes used in the fabrication of the MOX fuel could reduce the gallium content to ~ 10 ppm.

The fission product yield of gallium is exceedingly small, therefore, it is present in irradiated LWR uranium dioxide (UO_2) and commercial MOX fuels at concentrations several orders of magnitude lower than the anticipated levels in MOX fuel containing WG plutonium. Thus, there is no commercial experience with LWR MOX fuels containing gallium at concentrations similar to those expected to result from the use of WG plutonium.

This report identifies and evaluates issues relating to gallium in LWR MOX fuels, particularly as to possible impacts on cladding materials. Because the form of gallium in the fuel could be of importance to its transport and corrosivity, the chemistry of gallium in MOX fuel is the first issue that is considered. The most likely forms of gallium in freshly fabricated WG MOX fuel are identified, and the effects of in-reactor irradiation and thermochemical environments on the physical and chemical forms of gallium are discussed. Likewise, it is important to know whether gallium, in whatever form, can be transported from its location in MOX to the cladding interface such that corrosion reactions are possible. Therefore, potential mechanisms for gallium transport in the fuel pellet are discussed next. Known and postulated cladding mechanisms are then reviewed, and the potential effect of gallium on cladding performance is presented. Finally, potential unresolved issues are presented, and the type of research and development (R&D) required to provide missing information is suggested.

This assessment is based on data and information available in early 1997 and will be updated as new information evolves from ongoing R&D programs at Los Alamos National Laboratory (LANL) and Oak Ridge National Laboratory.

2. GALLIUM IN WG MOX FUEL

2.1 AS-FABRICATED WG MOX FUEL

Little to no information has been published or is otherwise available for MOX fuel that contains gallium in quantities expected from manufacture using WG plutonium. Therefore, no comparative information for gallium-containing MOX vs conventional MOX is available. This lack of information, especially for newly fabricated fuels, results in the need for confirmation of the inferences at many of the boundary conditions assumed in this report. At the 1% gallium level in plutonium, a typical MOX fuel assembly would contain 210 g of gallium. This compares with 5 g of gallium in a fuel assembly that contains 10 ppm gallium (reduction occurs during fabrication), or 10 mg of gallium because of fission product yield when no initial gallium is present in an assembly.*

2.2 CHEMISTRY

The chemistry of gallium in MOX fuel may be influenced by its distribution. This section considers two possibilities: (1) a second phase agglomerate of plutonium dioxide (PuO_2) containing Ga, and (2) Ga uniformly distributed either as an individual phase or in a solution of $(\text{U,Pu})\text{O}_2$.

2.2.1 Agglomerates

Depending on the MOX fuel preparation process, the plutonium (and gallium) may be present as second-phase agglomerates within the larger volume of UO_2 . The implications of this assumption are considered in this section.

2.2.1.1 Oxidation potential

It is important to know the state of the gallium (elemental or oxide) that may be present with plutonium as PuO_2 . Currently, no gallium-oxygen phase diagram is available. The one condensed gallium-oxide phase known with confidence is Ga_2O_3 (sesquioxide), but evidence exists for a gallium oxide (Ga_2O) suboxide phase, which has been reported to decompose at approximately 1075 K.¹ Some limited thermochemical information is also available in the data

* These calculations are based on a pressurized-water reactor with 21 kg of plutonium and 441 kg of uranium, for a total of 524 kg heavy metal oxide.

base of the "HSC Chemistry for Windows" software distributed by Outokumpu Research of Finland,² which indicates the phase Ga_2O as having a melting point of 925 K. These thermochemical data are in general agreement with a heat of reaction determined by Klemm and Schnick.³ Given the paucity of thermodynamic information about the suboxide phase, it has not been included in the following thermodynamic analysis, but it should be considered when more information is developed. However, the suboxide will form at lower oxygen activity than does Ga_2O_3 ; therefore, neglecting its presence should be a conservative assumption. Depending on the oxygen potential,* gallium is assumed to be present as the metal or the sesquioxide, Ga_2O_3 .

The thermodynamic data of Barin⁴ contain the unique set of oxygen potential-temperature values at which both the metal and oxide coexist and which serve as the boundary separating the formation of the stable oxide from elemental gallium. These values are plotted in Fig. 1 and are indicated by the line labeled Ga- Ga_2O_3 . The chemical potential of oxygen increases with increasing temperature indicating that the oxide becomes less stable. At the intersection points of Ga- Ga_2O_3 line with the lines determined by oxygen potential-temperature values for the coexistence of other metal-oxide phases, a temperature is indicated for equal stability of Ga_2O_3 and the other oxide. Where the Ga- Ga_2O_3 line is below that of the other oxide (i.e., more negative), Ga_2O_3 is more stable. However, where the Ga- Ga_2O_3 line is above that of the other oxide (i.e., less negative), elemental gallium can exist.

The oxygen potential (stability) of the PuO_2 phase can be compared to that of the gallium/gallium oxide (Ga- Ga_2O_3) boundary. Plutonium dioxide has a wide homogeneity range, with oxygen potential values measured for values of x in PuO_{2-x} as large as 0.3676.⁵ Thus, the dioxide phase can be substantially substoichiometric with resultant oxygen potentials significantly lower than that of nominal PuO_2 . A representation of the chemical thermodynamic behavior of PuO_{2-x} by Besmann and Lindemer⁶ can be used to determine the oxygen potential as a function of composition and temperature. The oxygen potential for stoichiometric PuO_2 , however, is not uniquely definable because in accordance with the phase rule, this invariant

* Oxygen potential is the chemical potential of oxygen and is defined as $RT \ln p^*[\text{O}_2]$, where R is the ideal gas law constant, T is absolute temperature in kelvin, and $p^*[\text{O}_2]$ is the oxygen partial pressure normalized to the standard-state partial pressure of 0.101 MPa (1 atm). This potential determines the stability of various oxygen-containing phases in a system. The variation in chemical potential with temperature and pressure can be expressed by the same equations as for free energy change; thus a decrease (more negative) in chemical potential indicates greater stability.

Figure 1. Metal-oxygen Ellingham diagram.

composition can exist over a range of oxygen pressures. PuO_2 is effectively a limiting composition because unlike the uranium-oxygen system, there are no condensed plutonium oxides with a higher oxygen-to-metal ratio (O/M) than 2.

To assess the state of gallium in an "agglomerate" of PuO_2 , it is assumed that the phase can be approximated by the behavior of $\text{PuO}_{1.9999}$, which is the highest oxygen content composition for which oxygen potential data have been measured.⁶ The temperature-oxygen potential relationship for PuO_2^* is given in Fig.1 based on the model of Besmann and Lindemer.⁶

At higher temperatures (>900 K), the PuO_2 line in the figure lies at oxygen potentials more positive than those for the $\text{Ga-Ga}_2\text{O}_3$ equilibrium, indicating that gallium will be present as the oxide with PuO_2 . Below ~ 900 K, the opposite prevails, and it is thus possible to have elemental gallium (in solution) in equilibrium with PuO_2 . (For comparison purposes, the fuel axial centerline temperature for an average rod ranges from 1173 to 1473 K, and the clad interface temperature ranges from 623 to 673 K.) *Thus, a very important conclusion from this analysis is, where the local oxygen potential is governed exclusively by the plutonium dioxide phase which is only slightly substoichiometric, elemental gallium can be present at relatively low temperatures.*

During burnup, oxygen is released in proportion to the fuel O/M, so that for every actinide atom fissioned, O/M oxygen atoms are released. Because PuO_2 is already in its highest oxidation state and cannot accommodate more oxygen, the fission products alone must react with the oxygen released to form oxide phases that tie up the oxygen. The free energy of the reaction to form these oxides governs the priority of the fission products which form oxides. The Ellingham diagram of Kleykamp⁷ indicates the oxygen potential boundaries for the formation of simple oxide fission product phases. Utilizing that information, supplemented by the thermochemical data from Barin,⁴ it is possible to determine the oxidation state of the fission products at a specific burnup.

A set of burnup calculations for 5% plutonium MOX fuel were performed to determine the fuel composition after 52.5 MWd/kg ($\sim 5\%$) burnup (upper end of the range of worldwide burnup experience), with the resultant fission product concentrations shown in Tables 1 and 2. It was also assumed that the entire initial concentration of 1% gallium in the original plutonium alloy was carried over to the fuel. Table 1 also assumes the fuel is prepared such that the gallium

* For convenience, $\text{PuO}_{1.9999}$ is written as PuO_2 .

Table 1. Fission product concentrations computed for a burnup of 52.5 MWd/kg and their oxidation state assuming gallium is present as the oxide in as-fabricated fuel

Fission Product and MOX	In Urania (Atoms/Atom of Initial Uranium)	In Plutonia Aggregate (Atoms/Atom of Initial Plutonium)	Total (Atoms/Atom of Initial Actinide)	Fission Product O/M in MOX	Oxygen in FP Oxide in Homogeneous MOX (Atoms/Atom of Initial Actinide)	Fission Product O/M in PuO ₂	Oxygen in FP Oxide in Plutonia Aggregate (Atoms/Atom of Initial Plutonium)
Se	8.75E-05	2.55E-03	2.11E-04				
Br	3.42E-05	1.00E-03	8.27E-05				
Kr	4.47E-04	1.13E-02	9.90E-04				
Rb	3.73E-04	9.71E-03	8.39E-04	1.00	8.39E-04	1.00	9.71E-03
Sr	9.49E-04	2.30E-02	2.05E-03	1.50	3.08E-03	1.50	3.45E-02
Y	4.91E-04	1.16E-02	1.05E-03	1.50	1.57E-03	1.50	1.74E-02
Zr	4.46E-03	1.24E-01	1.04E-02	2.00	2.08E-02	2.00	2.48E-01
Nb	6.56E-05	7.39E-04	9.93E-05	2.00	1.99E-04	2.00	1.48E-03
Mo	5.00E-03	1.58E-01	1.26E-02	2.00	2.53E-02	2.00	3.16E-01
Tc	1.20E-03	3.51E-02	2.90E-03			2.00	7.01E-02
Ru	4.67E-03	1.47E-01	1.18E-02			0.72	1.06E-01
Rh	9.60E-04	2.68E-02	2.25E-03				
Pd	3.11E-03	1.28E-01	9.37E-03				
Ag	2.34E-04	7.84E-03	6.14E-04				
Cd	2.62E-04	1.36E-02	9.27E-04			1.00	1.36E-02
Sn	1.09E-04	3.74E-03	2.90E-04			2.00	7.48E-03
Sb	3.13E-05	9.06E-04	7.50E-05			1.50	1.36E-03
Te	6.51E-04	2.08E-02	1.66E-03			2.00	4.16E-02
I	3.76E-04	1.19E-02	9.54E-04				
Xe	6.29E-03	1.94E-01	1.57E-02				
Cs	3.66E-03	1.16E-01	9.30E-03	1.00	9.30E-03	1.00	1.16E-01
Ba	1.53E-03	5.15E-02	4.03E-03	1.00	4.03E-03	1.00	5.15E-02
La	1.28E-03	3.94E-02	3.18E-03	1.50	4.78E-03	1.50	5.91E-02
Ce	2.84E-03	8.29E-02	6.84E-03	1.50	1.03E-02	1.50	1.24E-01
Pr	1.13E-03	3.53E-02	2.84E-03	1.50	4.26E-03	1.50	5.29E-02
Nd	3.57E-03	1.13E-01	9.04E-03	1.50	1.36E-02	1.50	1.69E-01
Pm	1.84E-04	3.26E-03	3.38E-04	1.50	5.07E-04	1.50	4.89E-03
Sm	8.00E-04	2.52E-02	2.02E-03	1.50	3.03E-03	1.50	3.78E-02
Eu	2.10E-04	7.64E-03	5.81E-04	1.50	8.72E-04	1.50	1.15E-02
Gd	1.38E-04	6.65E-03	4.64E-04	1.50	6.96E-04	1.50	9.98E-03
Tb	4.45E-06	1.91E-04	4.23E-06	1.50	6.34E-06	1.50	2.87E-04
Dy		1.06E-04	5.32E-06	1.50	7.98E-06	1.50	1.60E-04
MOX					5.00E-03		
				Total	1.08E-01		1.50
				Oxygen Released	1.08E-01		1.50

Table 2. Fission product concentrations computed for a burnup of 52.5 MWd/kg and their oxidation state assuming gallium is present unoxidized in as-fabricated fuel

Fission Product Ga and MOX	In Urania (Atoms/Atom of Initial Uranium)	In Plutonia Aggregate (Atoms/Atom of Initial Plutonium)	Total (Atoms/Atom of Initial Actinide)	Fission Product O/M in MOX	Oxygen in FP Oxide in Homogeneous MOX (Atoms/Atom of Initial Actinide)	Fission Product O/M in Plutonia	Oxygen in FP Oxide in Plutonia Aggregate (Atoms/Atom of Initial Plutonium)
Se	8.75E-05	2.55E-03	2.11E-04				
Br	3.42E-05	1.00E-03	8.27E-05				
Kr	4.47E-04	1.13E-02	9.90E-04				
Rb	3.73E-04	9.71E-03	8.39E-04	1.00	8.39E-04	1.00	9.71E-03
Sr	9.49E-04	2.30E-02	2.05E-03	1.00	2.05E-03	1.00	2.30E-02
Y	4.91E-04	1.16E-02	1.05E-03	1.50	1.57E-03	1.50	1.74E-02
Zr	4.46E-03	0.1237928	1.04E-02	2.00	2.08E-02	2.00	2.48E-01
Nb	6.56E-05	7.39E-04	9.93E-05	2.00	1.99E-04	2.00	1.48E-03
Mo	5.00E-03	1.58E-01	1.26E-02	2.00	2.53E-02	2.00	3.16E-01
Tc	1.20E-03	3.51E-02	2.90E-03			2.00	7.01E-02
Ru	4.67E-03	1.47E-01	1.18E-02			0.43	6.33E-02
Rh	9.60E-04	2.68E-02	2.25E-03				
Pd	3.11E-03	1.28E-01	9.37E-03				
Ag	2.34E-04	7.84E-03	6.14E-04				
Cd	2.62E-04	1.36E-02	9.27E-04			1.00	1.36E-02
Sn	1.09E-04	3.74E-03	2.90E-04			2.00	7.48E-03
Sb	3.13E-05	9.06E-04	7.50E-05			1.50	1.36E-03
Te	6.51E-04	2.08E-02	1.66E-03			2.00	4.16E-02
I	3.76E-04	1.19E-02	9.54E-04				
Xe	6.29E-03	1.94E-01	1.57E-02				
Cs	3.66E-03	1.16E-01	9.30E-03	1.00	9.30E-03	1.00	1.16E-01
Ba	1.53E-03	5.15E-02	4.03E-03	1.00	4.03E-03	1.00	5.15E-02
La	1.28E-03	3.94E-02	3.18E-03	1.50	4.78E-03	1.50	5.91E-02
Ce	2.84E-03	8.29E-02	6.84E-03	1.50	1.03E-02	1.50	1.24E-01
Pr	1.13E-03	3.53E-02	2.84E-03	1.50	4.26E-03	1.50	5.29E-02
Nd	3.57E-03	1.13E-01	9.04E-03	1.50	1.36E-02	1.50	1.69E-01
Pm	1.84E-04	3.26E-03	3.38E-04	1.50	5.07E-04	1.50	4.89E-03
Sm	8.00E-04	2.52E-02	2.02E-03	1.50	3.03E-03	1.50	3.78E-02
Eu	2.10E-04	7.64E-03	5.81E-04	1.50	8.72E-04	1.50	1.15E-02
Gd	1.38E-04	6.65E-03	4.64E-04	1.50	6.96E-04	1.50	9.98E-03
Tb	4.45E-06	1.91E-04	4.23E-06	1.50	6.34E-06	1.50	2.87E-04
Dy		1.06E-04	5.32E-06	1.50	7.98E-06	1.50	1.60E-04
Ga		3.35E-02	1.68E-03	1.50	2.51E-03	1.50	5.03E-02
MOX					3.00E-03		
				Total	1.08E-01		1.50
				Oxygen Released	1.08E-01		1.50

is present as the oxide, whereas Table 2 assumes the gallium in the fuel is elemental (lower O/M fuel). The fission product atoms formed per initial atom of either uranium or plutonium are given in the second and third columns of both tables. The second column shows the fission product concentration because of fissioning of uranium and uranium transmuted to ^{239}Pu , and the third column shows the concentration because of fissioning of the initial ^{239}Pu in the as-fabricated fuel. The fourth column shows the proportional sum of the previous two columns and is the total fission product inventory. The tables also give the O/M ratio for each of the fission products that form oxides based on the release of oxygen during fissioning and their thermochemistry. If an O/M value is not given, it means that either the element does not form an oxide or that the oxygen potential is insufficient to form the metal oxide. Column six represents the amount of fission-released oxygen consumed by the fission products in forming oxides per atom of initial actinide atom. The fission products were allowed to form oxides based on their thermochemical affinity for oxygen until all the fission-released oxygen was consumed. Note that, with the exception of cesium and rubidium, which are assumed to form uranates, all the fission products that oxidize are assumed to form simple oxides. The formation of complex oxides is considered in the later section on fission products. The initial O/M of the fuel is assumed to be 2.

The last two columns in Tables 1 and 2 were developed assuming the fuel contains isolated aggregate grains of plutonia in which all the gallium resides, with the fission products bred solely into the plutonia accommodating the fission-released oxygen. In the case where gallium is present as the oxide in as-fabricated fuel (Table 1), gallium is expected to remain as the oxide during burn-up. A number of the metallic fission products will form oxides, either in solution with the fuel or as independent phases, as indicated in Table 1.

The oxide phases that will form are seen to be somewhat different from those observed in typical LWR fuel.⁷ LWR fuel will have metallic precipitates containing molybdenum, technetium, cadmium, tin, antimony, and tellurium; however, under the assumption that in the MOX fuel the plutonia remains as an isolated aggregate, these metals are present as oxides. The oxygen balance also indicates a portion of the ruthenium will exist as oxide [i.e., the O/M ratios in Tables 1 and 2 are a fraction of the value of 2 for ruthenium dioxide (RuO_2)]. The presence of these fission products as oxides instead of metallic precipitates should not have a negative effect on fuel behavior unless they form precipitates whose volume increase causes mechanical deformation.

However, if gallium is elemental in the unirradiated fuel, it will form an oxide phase with fissioned-released oxygen. As shown in Table 2, gallium present at the 1 mass % level has little effect on the oxidation state of the fission products.

2.2.2 Bulk Fuel Chemistry

In this section we assume that the MOX fuel exists as a true solid solution of 5% plutonia (with gallium) in urania, and we can consider the phase as $U_{0.95}Pu_{0.05}O_{2\pm x}$.

2.2.2.1 Oxide formation

Besmann and Lindemer,⁶ as an extension of the work on PuO_{2-x} , have developed a chemical thermodynamic representation of the fluorite structure MOX. The equations detailing the representation are complex and are not included in this report, but can be found in ref. 6. Utilizing these relationships, the temperature-oxygen potential relationship for $U_{0.95}Pu_{0.05}O_{2\pm x}$ can be determined and the expressions for the nominal production stoichiometries of $U_{0.95}Pu_{0.05}O_2$, $U_{0.95}Pu_{0.05}O_{2.002}$, and $U_{0.95}Pu_{0.05}O_{1.995}$ are plotted in Fig. 1. The slopes of the lines are significantly different from those for PuO_2 . For comparison purposes, the line for stoichiometric UO_2 is also shown. The Ga- Ga_2O_3 equilibrium exists at a more positive oxygen potential above ~1260 K for $U_{0.95}Pu_{0.05}O_2$. This implies that should the $U_{0.95}Pu_{0.05}O_2$ phase determine the oxygen potential, Ga_2O_3 can only be reduced to the metal in regions of the fuel above ~1260 K. However, should the oxygen potential be determined by $U_{0.95}Pu_{0.05}O_{1.995}$, elemental gallium would be the stable phase over the entire temperature range. Finally, hyperstoichiometric $U_{0.95}Pu_{0.05}O_{2.002}$ would allow gallium to remain an oxide over the entire temperature range.

Again, for the homogeneous fuel, during burnup most of the metallic fission products can form oxide phases. In addition, unlike pure plutonia, the fuel can accommodate more oxygen in its fluorite structure. As a result, the oxygen balances in Tables 1 and 2 for homogeneous fuel were computed to leave a small fraction of oxygen that can combine with the fuel, thereby increasing the hyperstoichiometry of the fuel. The chemical state of the fission products are essentially the same as for typical LWR fuel.

Thus, for two scenarios, [gallium with PuO_{2-x} (below 900 K) and $U_{0.95}Pu_{0.05}O_{2-x}$ (for the entire temperature range shown in Fig. 1)] substoichiometric dioxide phases can lead to the presence of gallium metal in the fuel. To minimize any differences between conventional MOX and gallium-containing MOX, it is necessary to ensure that the gallium is oxidized, thus allowing

for the oxidation of most metallic fission products. This can be achieved by ensuring that the initial gallium is fully oxidized and that the initial O/M ratio of the MOX is at least 2.

2.2.3 Reactions with Fission Products

Ga_2O_3 reacts with rare earth oxides to form two types of compounds: LnGaO_3 and $3\text{Ln}_2\text{O}_3 \cdot 5\text{Ga}_2\text{O}_3$, where Ln is a rare earth element.¹ In addition to these rare earth oxide— Ga_2O_3 compounds, complex gallates of the type $\text{GaLnGa}_3\text{O}_7$, where Ln = La, Pr, Nd, or Sm, have been reported.⁴

Ga_2O_3 , heated with barium carbonate forms $\text{BaO} \cdot \text{Ga}_2\text{O}_3$. It is likely that the same gallate would form with BaO and Ga_2O_3 as the starting materials. Similarly, compounds of the type $\text{M}_2\text{O} \cdot 6\text{Ga}_2\text{O}_3$, where M = Rb or Cs are formed by sintering the alkali metal (Rb or Cs) carbonate with Ga_2O_3 .

Although elemental gallium reacts with iodine to form gallium iodide (GaI_3), this reaction will not occur in the presence of fission products La, Ba, or Cs or Zr from the cladding. Furthermore, Ga_2O_3 will not be converted to the iodide by reaction with iodine.

Accordingly, the most probable reactions of fission products with gallium will lead to the formation of mixed oxides with rare earths, alkaline earths, or alkali metals. These reactions would reduce the chemical activity of the gallium (increased gallium thermodynamic stability) compared to its initial activity in the absence of fission products; however, the melting points of the fission product compounds could be decreased and the volatility increased compared to Ga_2O_3 (increased tendency for gallium transport).

2.3 GALLIUM TRANSPORT MECHANISMS WITHIN FUEL

Given that gallium is present in the fuel, before it can react with the cladding, it must be able to collect at the fuel-cladding interface. Two possible transport mechanisms, gas phase and solid-state diffusion, are discussed in this section.

2.3.1 Gas Phase Transport

Possible mechanisms for gas phase transport are simple vaporization and condensation and chemical vapor (coupled) transport. Near the oxygen potentials for MOX fuel, as shown in Fig. 1, the dominant gaseous species will be Ga_2O . The only other gaseous species are elemental gallium and GaO, with only the gallium vapor pressure exceeding that of Ga_2O at oxygen

potentials well below those of the Ga-Ga₂O equilibrium. The Ga₂O vapor pressures in the presence of Ga₂O₃ are governed by the reaction:

Using the thermochemical data of Table 3, the oxygen potential expression for values of the vapor pressure of Ga₂O(g) over Ga₂O₃(l) is

$$RT \ln p_{O_2}^* = 970137 - 371.441 T + RT \ln p_{Ga_2O} .$$

Table 3. Thermodynamic values at 1000 K for the gallium-oxygen system .

		Ga(l)	O ₂ (g)	Ga ₂ O ₃	Ga ₂ O(g)	GaO(g)
ΔH _f [°]	kJ/mol	—	—	-1091208.	-121071	133973.
S [°]	J/(mol K)	91.859	243.578	220.136	347.999	279.381

Source: I. Barin Thermochemical Data of Pure Substances, VCH, Germany (1989).

At lower oxygen potentials, where elemental gallium is the stable condensed phase as opposed to the oxide, the vapor pressure of Ga₂O is determined from:

Using the data of Table 3, the oxygen potential can be expressed as:

$$RT \ln p_{O_2}^* = -242142 - 84.984 T + RT \ln p_{Ga_2O} .$$

At temperatures >1200 K, the vapor pressure of gaseous Ga₂O will be of the order of 10⁴ to 10⁵ Pa. In a temperature gradient within the fuel pin, the oxide species may largely vaporize in the hotter regions causing transport of the gallium oxide to the cooler clad surfaces where it

will condense. The above vapor pressures presume that the condensed gallium species are present as separate phases within the fuel, yet no reason exists why gallium, regardless of its oxidation state, could not be dissolved in the fluorite structure of the fuel. In that case, the equilibrium behavior of the gallium would be modified by its solution in the fuel and be governed by its activity in the solution. In the absence of data with regard to the activity of gallium in either plutonia or urania-plutonia, the best assumption, as demonstrated by LANL,⁸ is to presume that no energetic interactions exist between the species and that the system acts as an ideal solid solution. That being the case, the activity of the dissolved gallium species would simply be in direct proportion to its concentration. As a result, the vapor pressure of Ga_2O , or any other gallium species such as those described by the previously noted expressions and shown in Fig. 1, would be reduced by a factor equal to the molar concentration of the dissolved gallium species:

$$p_{Ga_2O(soln.)} = \frac{Ga}{Ga_2O_3(soln.)} p_{Ga_2O} ,$$

where $[Ga/Ga_2O_3]$ is the molar concentration of either elemental gallium or Ga_2O_3 in the MOX fuel. This reduction would be significant because of the low concentration of gallium present. *Figure 1 shows that elevated oxygen pressures suppress the Ga_2O vapor pressure over Ga_2O_3 , and thus significant burnup could serve to reduce gallium transport.*

With no other gallium-containing, relatively high vapor pressure species with which Ga_2O can form a vapor transport couple, deposition of metallic gallium on the clad via such a process is not possible. As noted earlier, this does not preclude simple vaporization of Ga_2O with subsequent condensation on the clad. Such gas-phase diffusion and deposition, however, would not be limited to the gallium system, but is possible for other, similarly behaving, fission product elements.

2.3.2 Solid-State Transport

In addition to any gas phase transport of gallium species to the fuel-clad interface, there are potential mechanisms by which gallium transport could occur in the solid state. These include the following:

- volume diffusion of gallium driven by gradients in gallium concentration (flux from high to low concentrations);
- enhanced concentration gradient driven volume diffusion where the flux of gallium is accelerated through grain boundaries, dislocations, etc.;
- volume diffusion of gallium driven by a temperature gradient (thermal diffusion) with the possibility that the gallium flux may be either up or down the temperature gradient;
- concentration gradient driven surface diffusion of gallium on either internal or external surfaces (e.g. cracks in the mixed oxide fuel);
- thermal surface diffusion of gallium from hot to cold regions; and
- irradiation-driven diffusion of gallium.

At the present time no information exists on which of these diffusion mechanisms may be effective in moving gallium to the fuel-clad interface during operation of the MOX fuel. Thermodynamically, it is expected that gallium will be present (based on expected fuel fabrication conditions) initially as Ga_2O_3 , and that this oxide should become increasingly stable as burnup progresses (see Sect. 2.2.1). It can be postulated that the volume diffusion of gallium in this chemical form could be relatively slow. However, if it is present as elemental gallium, transport is expected to be faster than if it is present as an oxide. Also, diffusive mass transport rates and dominant mechanisms should be expected to change continuously as burnup progresses and the original structure and nature of the MOX fuel is changed and degraded. For example, cracking of the fuel pellets will occur as a result of thermal cycling, and this would tend to increase the importance of surface diffusion internal to the fuel pellets as a gallium transport mechanism. Such cracking could also provide an avenue for gas phase transport.

As indicated in Sect. 2.2.1, the gallium may likely be concentrated in the PuO_2 agglomerates. This will provide local concentration gradients favoring movement of the gallium into the UO_2 matrix. Because no significant overall concentration gradient of gallium relative to the bulk fuel pellet is expected, there should be little driving force for transport of gallium to the fuel-clad interface as a result of concentration-dependent diffusion mechanisms. Also, early in the life of the MOX fuel when plutonium agglomerate fissions predominate, locally higher temperatures will likely occur in the agglomerates. This would provide local temperature gradients to further disperse gallium into the matrix but only if the thermal diffusion characteristic of the gallium diffusing species in MOX fuel is a flux from high to low temperatures. There is a larger potential for thermal diffusion, both volume and surface, as a

result of the very large radial temperature gradients in the MOX fuel pellets. (Axial gradients will also exist but will be much less severe.) Although any thermal surface diffusion that occurs will be from high to low temperatures (toward the fuel-clad interface), the direction of the gallium flux in the bulk material is not currently known.

In summary, neither the dominant mechanisms by which gallium might be transported in the MOX fuel matrix in the solid state nor the rates for such transfer mechanisms are known. This is further complicated by the physical and chemical changes expected in the fuel as burnup progresses. Therefore, it is impossible at present to predict whether gallium will be transported to the fuel-clad interface as a result of solid-state transport mechanisms.

3. CLAD PERFORMANCE AND DEGRADATION MECHANISMS

3.1 INTRODUCTION

This section discusses any likely impacts of gallium on the known corrosion mechanisms of Zircaloy with water and MOX fuel, respectively, and if these additional potential mechanisms need to be evaluated. Within the limitation of the available data, consideration is given to other types of corrosion/cracking mechanisms that could be introduced by the presence of gallium.

As a result of their overall favorable nuclear, mechanical, and corrosion properties, zirconium alloys (i.e., Zircaloy and Zr-Nb) are used as fuel cladding in water-cooled reactors. Alloying elements include Sn, Fe, Cr, and Nb, and extensive work has been done to determine how these alloying additions affect corrosion. With the exception of tin, these alloying elements have very low solubilities in zirconium and form second-phase particles if slowly cooled from the beta phase or if annealed in the alpha phase after rapid cooling from the beta phase.

The amount of alloying element in the matrix and second-phase particles, and the particle size distribution determine resistance to both uniform and localized accelerated (nodular) corrosion in water, the effect depending on concentration and morphology. Corrosion studies have generally focused on uniform corrosion of Zircaloy-4 in PWRs and on nodular formation on Zircaloy-2 in boiling water reactors (BWRs). Other important aspects of water-side corrosion include stress corrosion cracking (SCC) of stainless steel components (e.g., recirculation-line cracking in BWRs), hydriding, and transport of radioactivity (radiation transport) to the heat exchangers.

Compatibility of Zircaloy cladding with UO_2 and MOX fuels has been examined both in- and out-of-pile. Under conditions of high burnup (both simulated and in-reactor), brittle failure of the cladding has been observed in the form of through-wall cracks that initiate at the inside tube surface. A pellet-clad interaction (PCI) mechanism has been described that involves local deformation and certain embrittling fission products. Studies have indicated that gaseous iodine or cadmium-containing environments play a critical role in PCI failures. Inner surface liners of zirconium have been effective in mitigating this type of failure in BWRs, and minimization of the stress and heating rate have been effective in PWRs.

Because the development of through-wall cracks in the cladding is of critical concern in assessing fuel-clad performance, several forms of corrosion that can produce cracking in metals must be considered relative to possible impacts of gallium. Four of the principal mechanisms that can lead to environmentally induced cracking are

- SCC,
- hydrogen embrittlement (HE),
- liquid metal embrittlement (LME), and
- solid metal induced embrittlement (SMIE).

Gas-phase embrittlement mechanisms are not listed separately from hydrogen embrittlement, but gaseous elements can produce similar effects as well. All of the cited forms of embrittlement require the presence of a tensile stress in the material but, in general, there are many differences in the circumstances under which they occur.

In aqueous environments, susceptible metals can undergo time-dependent subcritical crack propagation, called SCC. Some confusion exists, however, because the term SCC has come to be used generically to describe any form of environmentally induced/stress-assisted cracking.

Cracking, blistering, hydride formation, and loss in tensile ductility are all forms of hydrogen damage or hydrogen embrittlement. Mechanisms that are of particular interest in the present evaluation are

- hydrogen trapping (i.e., bonding of hydrogen to impurities or defects);
- hydride formation (i.e., formation of a brittle phase that cracks easily);
- decohesion (i.e., lowering of the cohesive force between metal atoms);
- enhanced plastic flow (i.e., atomic hydrogen enhanced dislocation motion); and
- internal pressure-induced cracking (i.e., accumulation of hydrogen at voids or grain boundaries causing high internal pressures that grow cracks).

LME is thought to result from the chemisorption-induced reduction in strength of atomic bonding in the solid material in regions of stress concentrations. This type of embrittlement is different from corrosion embrittlement that can occur from intergranular penetration in the absence of stress. With LME, grain boundary penetration before the initiation of cracking does not appear to occur; however, several prerequisites are generally applicable:

- tensile stress,
- plastic flow,
- polycrystalline material, and
- wetting/chemisorption.

Other observations relative to LME have been that only certain (but unpredictable) combinations of materials are susceptible; LME is unlikely when high mutual solubility exists between solid and liquid metals; LME is unlikely when the liquid and solid metal form a high

melting intermetallic compound; LME is more severe near the melting temperature of the liquid metal and usually decreases with increasing temperature; and a rapid change from no embrittlement to embrittlement can occur if the tensile strength of the alloy increases, such as is likely during irradiation.

SMIE generally has similar prerequisites as LME. However, incubation periods are much longer, indicating that the crack initiation process is different. Overall rates are also much slower.

3.2 FUEL-SIDE CORROSION

Fuel-side corrosion refers to the corrosion that may occur on the fuel-side of the cladding.

3.2.1 Environment/Burnup

The effect of gallium on fuel-side corrosion will depend on several factors (discussed previously) that are influenced both by fuel fabrication processing and chemical and physical changes accruing in the fuel during burnup:

- the concentration and morphology of gallium-distributed uniformly as a solute or distributed as dispersed agglomerates;
- the oxidation potential of the as-fabricated oxide fuel;
- changes in oxidation potential resulting from fission product buildup, transmutation of gallium, and gallium transport to the cladding;
- chemical reaction of the gallium with fission products and fuel constituents; and
- changes in fuel density and porosity and breakup of the fuel.

The products accruing from gallium transmutation (principally germanium) will be at such low concentrations in the fuel that they should not contribute to the normal degradation of cladding by fission products.

In Sect. 2.1, two levels of concentration of gallium were mentioned: 1% in the plutonium used to make MOX fuel and 10 ppm in processed fuel. At the 1% level, the gallium could influence overall chemistry of the fuel during its life whereas at 10 ppm, it seems unlikely to do so. As discussed in Sect. 2.2, the oxygen potential of the reference MOX fuel at reactor startup can be such that either gallium or Ga_2O_3 is stable. Substoichiometry of the MOX fuel and higher

temperature favor the stability of gallium. However, fission physics calculations indicate that the oxidation potential will increase and should exceed that needed for the stabilization of Ga_2O_3 during fuel burnup.

As discussed in Sect. 2.2.3, the interaction of gallium with fission products in MOX fuel could potentially lead to the formation of mixed oxides between Ga_2O_3 and rare earths, alkaline earths, or alkali metals. None of these reactions would be expected to affect corrosion of the cladding compared to reactions occurring in MOX fuels without gallium. Likewise, gallium is not expected to affect the chemical state of the fission product iodine, one of the principal contributors to PCI failures (Sect. 2.2.3). The one class of fission product interaction with Zircaloy cladding which gallium could enhance involves elements that potentially can cause LME. Based on laboratory tests, cadmium (in oxide fuel) has been shown to induce Zircaloy cracking, and the mechanism has been attributed to LME. Accordingly, it is possible that any LME effects related to the fission product cadmium could be magnified when gallium is also present (i.e., a synergism may exist between the LME effects of cadmium and gallium, as discussed in the next section).

Transport of gallium (Section 2.3) in the system depends upon a number of factors, most of which cannot be quantified at this time. However, the corrosion mechanisms that are discussed below generally presume some method for gallium transport.

3.2.2 Material Variables

Because the solubilities of gallium in zirconium and zirconium in gallium at temperatures of interest are relatively low,⁹ any interalloying of gallium with the Zircaloy cladding should lead to the formation of intermetallic compounds, which are characteristically brittle. However, given the small amount of gallium in the fuel compared to the surface area and volume of cladding, such interalloying (corrosion) would be superficial, and apart from the possibility of grain boundary embrittlement discussed in Sect. 3.2.4, is not expected to affect the metallurgical integrity of the cladding. Gallium does form a low-melting eutectic system with tin, a minor alloying addition to Zircaloy. However, considering that tin is present as a dilute solid solute in a zirconium solvent, it is unlikely that tin-gallium eutectic will form by the diffusion of trace quantities of gallium into the cladding. While the collection of liquid gallium on the cladding surface could in principle dissolve tin from the alloy, the mass of gallium is likely too small for this effect to impact the chemistry or metallurgy of the cladding.

3.2.3 Pellet Clad Interaction

Pellet-clad interaction leading to failure in Zircaloy fuel cladding has been attributed to the presence of stresses in the cladding and one or more aggressive chemical species. The aggressive chemical species arise from fission products generated and released during power generation. The stresses arise from the mismatch in thermal expansion of the oxide fuel pellet and that of the Zircaloy in combination with frictional forces.¹⁰ Under conditions of power changes, released fission products and stresses are present simultaneously. The resulting brittle failure involves longitudinal through-wall cladding cracks initiated at the inside tube surface. A failure with iodine as the aggressive chemical species has been reported in the literature as SCC,^{11, 12} and a failure with cadmium as the aggressive species has been reported as LME. An inner surface liner of zirconium was found to be effective in preventing this type of failure.¹³ As discussed previously, gallium is not expected to significantly affect interactions of Zircaloy with fission products with the possible exception of cadmium that is addressed in the next section.

Gallium, if present as Ga_2O_3 , could potentially intermix with the normally protective zirconium dioxide (ZrO_2) on the interior of the Zircaloy cladding. Such intermixing could be deleterious if it resulted in a lowering of the ZrO_2 melting point. Although we could find no phase diagram for the Ga_2O_3 - ZrO_2 system, both oxides have relatively high melting points, and the effect of intermixing would not be expected to lower the melting point to an extent that would affect oxide performance.

One potentially serious effect of gallium on pellet-clad interaction relates to LME and is discussed in the following section.

3.2.4 Mechanisms of Gallium Embrittlement

Zircaloy is known to be embrittled by the presence of certain low melting heavy metals, mercury being a notable example. The effect is associated with the phenomenon termed LME (See Sect. 3.1). By this mechanism, relatively low concentrations of a liquid metal can lead to decohesion of the host metal, especially along grain boundaries, which in turn could lead to stress-assisted cracking.

It has been demonstrated experimentally that gallium can cause embrittlement of structural alloys at temperatures in the range of operating LWRs. The best known examples relate to aluminum alloys, which fail catastrophically under low stresses in the presence of gallium. Experiments relative to embrittlement of zirconium alloys by gallium have been inconclusive with respect to LWR service. Grubb et al.¹⁰ performed constant extension rate tests

of Zircaloy-2. At a temperature of 573 K (300°C) and constant extension rate of 0.85 $\mu\text{m/s}$ (0.002 in/min), it was found that Zircaloy-2 was not embrittled when high purity gallium was added to cesium. Under these same conditions, the fission products strontium, yttrium, cadmium, as well as iodine in cesium, were found to embrittle Zircaloy-2. Recently, Cox et al¹⁴, using compact tension specimens, found that tests of Zr-2.5% Nb with liquid Ga at 303 K (30°C) did not show transgranular cracking, but did show rather limited intergranular cracking. The cracking was considered to be limited by the poor wetting of zirconium by gallium.

To induce embrittlement of the Zircaloy cladding, gallium would need to be present in the form of reduced metal and in intimate contact with the metallic Zircaloy substrate. This would require transport of gallium from the fuel pellet, where it is expected to be Ga_2O_3 , to the Zircaloy cladding. Potential mechanisms for such transport, although not readily predictable, were outlined in Sect. 2.3.2. A further requirement would be a break in the protective oxide (ZrO_2) overlaying the Zircaloy cladding (or zirconium liner, if one is present). Conditions at this point would be conducive to the formation of metallic gallium by reaction with zirconium (See Fig. 1.), such as

or

Although the bulk concentration of gallium in the fuel is relatively low, if the above conditions were met, even small amounts of gallium could potentially be damaging because the reduction of gallium would be localized at a crack tip, where a reactive zirconium metal surface is being created continuously to drive these reactions.

Cadmium, present as a fission product in LWR fuel, has been shown experimentally to reduce the ductility of Zircaloy. Because cadmium is a relatively low melting [594 K (321°C)] metal, its effect on Zircaloy is symptomatic of LME. The possibility of a synergism between the known effect of cadmium and the added presence of gallium will need to be examined.

3.3. WATERSIDE CORROSION

Waterside corrosion refers to processes by which primary reactor vessel components react with cooling water. Components include fuel rods as well as stainless steel piping, the pressure vessel, and hard facings on pumps and valves. Many of these processes have been studied for more than thirty years and are well documented.¹⁵ Uniform corrosion (oxidation), nodular corrosion (accelerated corrosion), SCC, radiation transport, and crud-induced localized corrosion are examples of the types of corrosion that have been investigated. This section will address the likely effects of gallium in MOX fuel on these mechanisms and the possibility that it would introduce different mechanisms.

In general, the parameters that affect the waterside corrosion performance of Zircaloy include materials characteristics (e.g., composition, microstructure), coolant conditions (temperature, pH, chemistry, particulates) and thermal hydraulic duty (power rating). If gallium enters the cladding, it could affect the material characteristics. Because gallium is initially present in the MOX fuel and not the clad, it starts out being isolated from the regions where corrosion reactions occur. Therefore, as has been previously stated, it must first penetrate the clad and be transported to the waterside-clad interface before it can participate. With a barrier liner for PCI protection, it would first have to penetrate the liner as well. Based on the relatively low diffusion rate of gallium, a substitutional element, at $\leq 300^{\circ}\text{C}$, atomic transport through the Zircaloy clad is not expected to be a viable transport mechanism. Rather, transport of gallium to the waterside would require some form of breach (a breached fuel pin would be detected and removed) to give water access to the clad-fuel annulus.

Uniform corrosion (oxidation) and hydriding depend upon the stability of the oxide film that forms on the outside surface of the clad that is in contact with water. The very high thermodynamic stability of ZrO_2 suggests that gallium would not impact the scale. Cations with an ionic radius much different from Zr^{+4} could produce lattice strains sufficient to crack the protective oxide; however, Ga^{+3} is approximately 0.8 times that of Zr^{+4} and so would not be expected to be highly detrimental even if it were somehow incorporated into the oxide.

Nodular corrosion is more difficult to assess. The process by which this type of accelerated corrosion occurs is not completely understood. Nodules appear to be initiated by the presence of intermetallic compounds between Zr and Fe and Cr, $\text{Zr}(\text{Cr}, \text{Fe})_2$. A debate remains as to whether these second-phase particles or associated solute depletion of matrix between these particles cause nodular nucleation. Most mechanisms assert that the location where production of atomic hydrogen (H°) occurs in the oxide determines susceptibility to nodular formation.

Retention of atomic hydrogen in the oxide damages the oxide and leads to accelerated corrosion, primarily in BWRs. Because mechanisms for nodule formation and oxide damage from atomic hydrogen are not well understood, it is difficult to assess the impact of gallium. However, if gallium behaves like aluminum and increases retention of hydrogen in MOX fuel, it could impact nodular corrosion if it were present in the ZrO_2 protective film.

Three primary factors affect intergranular stress corrosion cracking (ISCC) of stainless steel in LWR primary water: stress, material susceptibility, and water chemistry. A fourth, radiation, has been observed to enhance ISCC by its effect on alloy sensitization and water chemistry. Because these are external to the fuel-clad assembly, gallium in MOX fuel should not affect any of these factors absent a fuel clad breach.

Given a fuel-clad breach of the size that would instigate an off-normal reactor shutdown, the global release of gallium would be extremely small in comparison with the volume of water in a 600–1200 MW LWR. Accordingly, the concentration of gallium, during the relatively short exposure time required for shutdown and after-cooling, would not be expected to affect the performance of any reactor component during the shutdown. Likewise, once the offending fuel element is removed, the residual concentration of gallium in the system would be below that which could affect reactor performance on resumption of operation. In the event of a more massive fuel-clad breach under accident conditions, there could be effects from the gallium that would add to or supersede the effects accruing from other chemical species during the accident, but little information exists by which to assess this possibility.

4. GALLIUM AND FUEL PERFORMANCE: CONCLUSIONS AND RECOMMENDATIONS

The fact that the concentration of gallium in MOX fuel would be very small does not necessarily mean that effects are likely to be small to negligible. Thermochemical, kinetics, materials, and corrosion science principles must be applied to evaluate potential effects. For example, although iodine is the most deleterious fission product element in PCI, no way exists to compare gallium with iodine because no connection is known relative to a particular corrosion mechanism. After iodine was identified as the main culprit in PCI, investigators have attempted to understand the mechanism (identified as SCC) and to determine the parameters that affect it.

In the case of gallium, it has been shown that without control of the stoichiometry of the MOX fuel it is possible for either elemental gallium or Ga_2O_3 to be present in the fuel. The temperature gradient across the fuel rod provides a potential driving force for vapor phase or solid-state transport of gallium to the fuel/clad interface, but whether it will occur is not clear. Dissolution of gallium in the fluorite structure MOX fuel would mitigate vapor phase transport, and at present, no data or information is available to permit prediction of the solid-state transport of gallium in MOX fuel. Neither dominant transport mechanisms for solid-state diffusion nor associated transport rates are known. The physical and chemical changes that will occur in the fuel during irradiation, together with the large and varying thermal gradients and cycles that will exist, further complicate any assessment of solid-state transport. Assuming that transport can occur, possible mechanisms for gallium-assisted corrosion of zirconium alloy cladding have been identified from the limited information available about the system. However, the gallium/cladding system must be experimentally evaluated to determine if the identified mechanisms do occur, how they are manifested, and what parameters impact the mechanisms and in what way. The issues raised relative to possible impacts of gallium in MOX on clad corrosion and recommended actions are as follows:

- To keep gallium as a metal oxide in as-fabricated fuel, the fuel O/M should be at least equal to 2.
- An understanding is needed of the oxidation state of gallium in as-fabricated and in-reactor fuel under the inclusive conditions where the content of gallium in fuel remains high (i.e., near the original concentration in weapons plutonium source material), where the gallium remains concentrated in PuO_2 aggregate particles in UO_2 , and where the fuel is fabricated at oxygen potentials such that elemental gallium (in solution) is present. Given this set of conditions, a more detailed understanding of the gallium-oxygen phase

diagram, including any suboxide phases, would allow an understanding of whether elemental gallium (in solution) is truly stable, or whether a suboxide phase forms.

- Reactions of fission products with gallium should lead to more stable compounds than Ga_2O_3 ; although, it is possible that increased transport would occur. However, LME effects related to cadmium could be increased, and this sensitivity should be determined experimentally as discussed below.
- No second vapor species are known with appropriate properties with which Ga_2O can form a vapor transport couple that could cause accumulation of a gallium phase at the clad surface. However, simple vaporization-condensation can occur in which the Ga_2O vapor species deposits the condensed phase Ga_2O_3 , particularly at fuel temperatures $>1200\text{ K}$ where Ga_2O vapor pressures can reach $10^4\text{--}10^5\text{ Pa}$. Higher oxygen potentials suppress the vapor pressure of Ga_2O (see Fig. 1), and because oxygen potential increases with burnup, the potential for vapor transport will decrease with burnup.
- General corrosion or alloying of the cladding with gallium or gallium oxide is not a concern because general corrosion is mass limited and the quantity of gallium present in the fuel volume is low relative to the clad volume. Thus, general corrosion could only affect the innermost surface region of the cladding.
- Localized corrosion (grain boundary penetration, crack tip interactions) and liquid-metal embrittlement by gallium are possible compatibility issues that should be further investigated. Such factors as low concentrations of Ga, the limited possibility of forming liquid Ga, Ga mass transport kinetics, use of a barrier liner and stable surface coatings, all mitigate the probability that these localized corrosion interactions will occur. However, experimental data are needed to confirm these suppositions. These experiments should consider the effects of:
 - physical state of gallium in prototypical fuel pellets
 - mass transport of gallium phase (oxide)
 - solid-state
 - vaporization and condensation
 - fuel rod temperature and temperature gradient
 - concentration and distribution of gallium
 - burn-up changes
 - physical state of the pellet
 - fission product interactions (e.g., cadmium)

- cladding material composition
- cladding material coatings
- The possibility that gallium will influence water corrosion is considered remote. Without a clad breach, gallium could only influence the sensitivity of the clad structure to stress SCC. However, the overall concentration of gallium is low, and it would have to reach the water-clad interface region by transport through the clad matrix. Some testing to demonstrate that low levels of gallium in Zircaloy cladding does not make the material subject to SCC in water should be sufficient to essentially eliminate this type of corrosion mechanism as a possibility. In the event of a breached fuel pin, a gallium compound would likely be taken into the water, but the concentration would be extremely low given the large volume of water in the primary system. Once again, some testing should be sufficient to demonstrate any possible effects on primary system components. Effects of gallium on spent fuel storage are similar to those just discussed. Temperatures are generally lower and materials other than Zircaloy and austenitic stainless steel will have to be included; however, the low concentration of gallium, especially in the absence of a failed fuel pin, makes deleterious corrosion effects highly unlikely.

REFERENCES

1. I. A. Sheka, L. S. Chaus, and T. T. Metyureva, *The Chemistry of Gallium*, Elsevier, New York, New York, 1966.
2. A. Roine, *Outokumpu HSC Chemistry for Windows*, Outokumpu Research Oy, Kuparitie, Finland, 1994.
3. W. Von Klemm, and I. Schnick, Die Bildungswarme von Gallium I-Oxyd, *Z. Anorg. Allgemeine Chemie* 226, 353-358 (1936).
4. I. Barin, *Thermochemical Data of Pure Substances*, VCH, Germany, 1989.
5. T. L. Markin, and E. J. McIver, "Plutonium 1965," pp. 845-57 in *Proc. of the Third Intl. Conf. on Plutonium*, Chapman and Hall, London 1967.
6. T. M. Besmann, and T. B. Lindemer, "Chemical Thermodynamic Representations of $\langle \text{PuO}_{2-x} \rangle$ and $\langle \text{U}_{1-z}\text{Pu}_z\text{O}_w \rangle$," *J. Nucl. Mater.* 130, 489-504 (1985).
7. H. Kleykamp, "The Chemical State of the Fission Products in Oxide Fuels," *J. Nucl. Mater.* 131, 221-246 (1985).
8. D. P. Butt, "Thermodynamic and Kinetics of Ga in MOX", LA-UR-97-3853, Los Alamos National Laboratory 1997.
9. T. B. Massalski, ed., *Binary Alloy Phase Diagrams*, Vol. 2, p. 1880, ASM International, Materials Park, Ohio, 1990.
10. W. T. Grubb, and M. H. Morgan III, "A Survey of the Chemical Environments for Activity in the Embrittlement of Zircaloy-2," pp. 145-154 in *Proceedings of the Fourth International Conference: Zirconium in the Nuclear Industry*, ASTM STP 681, American Society for Testing and Materials, Philadelphia, Pa., 1979.
11. H. S. Rosenbaum, *Electrochemical Technology*, Vol. 4, p. 153 (1966).
12. H. S. Rosenbaum, J. H. Davies, and J. Q. Pon, EURAEC Report, GEAP 5100-5105, 1966.
13. D. S. Tomalin, R. B. Adamson, and P. R. Gangloff, "Performance of Irradiated Copper and Zirconium Barrier-Modified Zircaloy Cladding Under Simulated Pellet-Cladding Interaction Conditions," *Proceedings of the Fourth International Conference: Zirconium in the Nuclear Industry*, pp. 122-144 in ASTM STP 681, American Society for Testing and Materials, Philadelphia, Pa., 1979.
14. B. Cox and Y. M. Wong, "Liquid Metal Embrittlement of Zr-2.5% Nb Alloy," submitted to *J. Nucl. Mater.* 1996.
15. G. J. Theus and J. R. Weeks, eds. *Proceedings of the Third International Symposium on Environmental Degradation of Materials in Nuclear Power Systems — Water Reactors*, The Metallurgical Society, Inc., Warrendale, Pa., 1987.

APPENDIX

PHYSICAL, CHEMICAL AND NUCLEAR CHARACTERISTICS OF GALLIUM AND GALLIUM OXIDES

A.1 ELEMENTAL GALLIUM

A.1.1 PHYSICAL CHARACTERISTICS

Gallium, a metal in Group III of the periodic table, has unusual thermal properties. It has a low melting point [302.93 K (29.78°C)], it vaporizes above 2473 K (2200°C), has the widest difference between melting and boiling points of any element. It expands during solidification, and it is easily super-cooled in the liquid state.¹ Gallium wets almost all surfaces. Some physical properties of gallium are listed in Table A.1. The boiling point is not known precisely because of the volatility of the oxide Ga₂O, which forms when gallium is heated in oxide vessels.²

Table A.1. Physical properties of gallium

Property	Value
Melting point °C.	29.78
Boiling point °C.	ca. 2200
Density at melting point (Mg/m ³)	5.904 solid 6.95 liquid
Heat of fusion (J/g)	79.8
Electrical resistivity (mΩ•m) (solid at 20°C) axes	a. 0.81 b. 54.3 c. 17.4
Electrical resistivity (mΩ•m) (liquid at 30°C)	27.795
Thermal conductivity W/(m•K) (solids at 20°C) axes	a. 88.4 b. 16.0 c. 40.8
Thermal conductivity W/(m•K) (liquid at 77°C.)	28.7

Source: Encyclopedia of Chemical Technology, Vol. 11, Wiley, New York, New York, 1994.

A.1.2 CHEMICAL CHARACTERISTICS

Gallium is chemically similar to aluminum but somewhat less reactive. It forms a protective oxide surface film in air that protects it from further oxidation. Gallium is amphoteric, but it is more acidic than aluminum. This property is used to separate gallium from aluminum. Gallium, like aluminum, is normally trivalent, Ga^{+3} . However, it may also be monovalent, Ga^{+1} . The halogens Br, Cl, and F react with gallium at ambient temperature. I, S, Se, Te, P, As or Sb react with hot Ga .²

At temperatures of 773–1273 K (500–1000°C) and above gallium reacts with most metals. Tungsten is one of the few metals that is unaffected by gallium.^{1,2} Gallium forms nine intermetallic compounds with zirconium and eleven with plutonium. These compounds are shown in Table A.2.

Table A.2. Gallium compounds with zirconium or plutonium

Zirconium*	Plutonium†
ZrGa_3	$\text{Pu}_2\text{Ga}_{15}$
ZrGa_2	PuGa_6
Zr_3Ga_5	PuGa_4
Zr_2Ga_3	$\text{PuGa}_{3.7}$
ZrGa	Pu_2Ga_7
Zr_5Ga_4	PuGa_3
Zr_3Ga_2	PuGa_2
Zr_5Ga_3	Pu_2Ga_3
Zr_2Ga	PuGa
	Pu_5Ga_3
	Pu_3Ga

(1982) Chojni, V.V. Akhachinskij, I. Ansora, and M.H. Rand, Bull. Alloy Phase Diagrams, 2(3), 488, 489, 490, 491, 492, 493, 494, 495, 496, 497, 498, 499, 500, 501, 502, 503, 504, 505, 506, 507, 508, 509, 510, 511, 512, 513, 514, 515, 516, 517, 518, 519, 520, 521, 522, 523, 524, 525, 526, 527, 528, 529, 530, 531, 532, 533, 534, 535, 536, 537, 538, 539, 540, 541, 542, 543, 544, 545, 546, 547, 548, 549, 550, 551, 552, 553, 554, 555, 556, 557, 558, 559, 560, 561, 562, 563, 564, 565, 566, 567, 568, 569, 570, 571, 572, 573, 574, 575, 576, 577, 578, 579, 580, 581, 582, 583, 584, 585, 586, 587, 588, 589, 590, 591, 592, 593, 594, 595, 596, 597, 598, 599, 600, 601, 602, 603, 604, 605, 606, 607, 608, 609, 610, 611, 612, 613, 614, 615, 616, 617, 618, 619, 620, 621, 622, 623, 624, 625, 626, 627, 628, 629, 630, 631, 632, 633, 634, 635, 636, 637, 638, 639, 640, 641, 642, 643, 644, 645, 646, 647, 648, 649, 650, 651, 652, 653, 654, 655, 656, 657, 658, 659, 660, 661, 662, 663, 664, 665, 666, 667, 668, 669, 670, 671, 672, 673, 674, 675, 676, 677, 678, 679, 680, 681, 682, 683, 684, 685, 686, 687, 688, 689, 690, 691, 692, 693, 694, 695, 696, 697, 698, 699, 700, 701, 702, 703, 704, 705, 706, 707, 708, 709, 710, 711, 712, 713, 714, 715, 716, 717, 718, 719, 720, 721, 722, 723, 724, 725, 726, 727, 728, 729, 730, 731, 732, 733, 734, 735, 736, 737, 738, 739, 740, 741, 742, 743, 744, 745, 746, 747, 748, 749, 750, 751, 752, 753, 754, 755, 756, 757, 758, 759, 760, 761, 762, 763, 764, 765, 766, 767, 768, 769, 770, 771, 772, 773, 774, 775, 776, 777, 778, 779, 780, 781, 782, 783, 784, 785, 786, 787, 788, 789, 790, 791, 792, 793, 794, 795, 796, 797, 798, 799, 800, 801, 802, 803, 804, 805, 806, 807, 808, 809, 810, 811, 812, 813, 814, 815, 816, 817, 818, 819, 820, 821, 822, 823, 824, 825, 826, 827, 828, 829, 830, 831, 832, 833, 834, 835, 836, 837, 838, 839, 840, 841, 842, 843, 844, 845, 846, 847, 848, 849, 850, 851, 852, 853, 854, 855, 856, 857, 858, 859, 860, 861, 862, 863, 864, 865, 866, 867, 868, 869, 870, 871, 872, 873, 874, 875, 876, 877, 878, 879, 880, 881, 882, 883, 884, 885, 886, 887, 888, 889, 890, 891, 892, 893, 894, 895, 896, 897, 898, 899, 900, 901, 902, 903, 904, 905, 906, 907, 908, 909, 910, 911, 912, 913, 914, 915, 916, 917, 918, 919, 920, 921, 922, 923, 924, 925, 926, 927, 928, 929, 930, 931, 932, 933, 934, 935, 936, 937, 938, 939, 940, 941, 942, 943, 944, 945, 946, 947, 948, 949, 950, 951, 952, 953, 954, 955, 956, 957, 958, 959, 960, 961, 962, 963, 964, 965, 966, 967, 968, 969, 970, 971, 972, 973, 974, 975, 976, 977, 978, 979, 980, 981, 982, 983, 984, 985, 986, 987, 988, 989, 990, 991, 992, 993, 994, 995, 996, 997, 998, 999, 1000.

At concentrations of ~1%, gallium stabilizes the δ phase of plutonium.¹

Selected chemical properties of gallium are shown in Table A.3.

Table A.3. Chemical properties of gallium

Configuration of outer electron shells	$4s^2 4p^1$
Ionic radius	62 pm ^a
Atomic radius	0.138 nm ^a
Atomic number	31
Atomic mass (60.1% ⁶⁹ Ga, 39.9% ⁷¹ Ga)	69.72 amu
First ionization potential	5.97 V ^b
Electrode potential $Ga \rightarrow Ga^{+3}(aq.) + 3e^-$	0.52 V ^b

Sources: ^a*Encyclopedia of Chemical Technology*, Vol. 11, Wiley, New York, New York, 1994.

^bW.M. Latimer, and T.H. Hildebrand, *Reference Book of Inorganic Chemistry*, 3rd ed., 150, Macmillan, New York, New York, 1951.

A.1.3 NUCLEAR CHARACTERISTICS OF GALLIUM

Naturally occurring gallium is made up of ⁶⁹Ga (60.1 %) and ⁷¹Ga (39.9 %). The capture cross section at 0.025 eV is 2.2 barns for ⁶⁹Ga and 3.7 barns for ⁷¹Ga. There is some capture resonance structure for both nuclides between 100 eV and 10,000 eV as shown in Fig. A.1. The capture resonance integral for ⁶⁹Ga is 18.2 barns and the capture resonance integral for ⁷¹Ga is 32.2 barns.

Gallium-69 captures to ⁷⁰Ga, which decays to germanium-70 (⁷⁰Ge) by beta decay with a 21.1-min half-life. Germanium-70 has a capture cross section at 0.025 eV of 2.9 barns. Gallium-71 captures to ⁷²Ga, which decays to ⁷²Ge by beta decay with a 14.1-h half-life. The 0.025 capture cross section of ⁷²Ge is 0.8 barns. The capture resonance integrals for ⁷⁰Ge and ⁷²Ge are 2.5 barns and 0.9 barns, respectively.

The fission yields of the gallium and germanium isotopes are very low compared to other fission products for both uranium and plutonium fissions. Thus, little gallium is in non-weapons-grade fuels.

Figure A.1(a). Gallium-69 capture cross section versus energy

Figure A.1(b). Gallium-71 capture cross section versus energy

A.2 GALLIUM OXIDES

Gallium combines with oxygen to form the oxides Ga_2O and Ga_2O_3 . The oxide GaO has been detected in the vapor state by spectroscopy. However, gallium does not readily have a valence of +2 so this oxide, even though it has been detected, will not be considered further.

Gallium suboxide (Ga_2O) forms when Ga_2O_3 is heated in a vacuum at 773 K (500°C) or by the reaction of Ga_2O_3 and Ga.^{1,2} At temperatures greater than 973 K (700°C) in vacuum, Ga_2O decomposes into Ga_2O_3 and Ga. Gallium suboxide exists as a dark brown solid and as a gas. Gallium suboxide is a strong reducing agent. It is oxidized to Ga_2O_3 by heating in air.²

There are five crystal modifications of Ga_2O_3 . The β (monoclinic) form is the most stable.^{1,2} Gallium oxide, Ga_2O_3 forms by heating gallium in air or by thermally decomposing gallium nitrate or hydroxide at 473-523 K (200-250°C).² It can be reduced by heating at ~873 K (600°C) in hydrogen or carbon monoxide. Gallium oxides are insoluble in water. Gallium forms an oxyhydroxide GaOOH by the reaction of gallium with steam at ~473 K (200°C).

A.3 IMPURITIES

The reaction of gallium or gallium compounds with impurities occurs in competition with other materials in the fuel and the cladding.

A.3.1 HALOGEN IMPURITIES

Fluorine reacts with all material in a fuel pin. Gallium forms the gallium fluoride (GaF_3). However other materials form more stable fluorides. The fission products La, Ba, or Cs, in the form of either metal or oxide will react with GaF_3 to form LaF_3 , BaF_2 , or CsF . The following reactions are expected:

and

In addition, zirconium would preferentially react with fluoride or fluorine:

Thus, any effect of a fluoride impurity would likely be because of its reactivity rather than because of the presence or absence of gallium.

Gallium reacts with the other halogens Cl, Br, and I to form compounds of the types GaX_3 and Ga_2X_4 , where X represents the halide. The GaX_3 compounds will not be stable in the presence of the fission products La, Ba, or Cs or Zr from the cladding. The reactions would be analogous to those previously shown for the fluorides. The Ga_2X_4 compounds can be written as $Ga^{+1}(Ga^{+3}X_4)$.¹ No thermochemical data exist for these compounds that could be used to evaluate their stability relative to other materials. However, these halides have gallium with a valence of +1 and +3. If the oxygen potential in the fuel is such that gallium would be in the fuel as Ga_2O_3 or a mixed oxide containing Ga^{+3} as is anticipated, the formation of Ga_2X_4 would require partial reduction of Ga^{+3} to Ga^{+1} . It is not apparent how this could occur.

Iodine and bromine are fission products. It is not likely that impurity concentrations of these elements would exceed their fission yield.

A.3.2 CHALCOGENIDE IMPURITIES

Gallium forms two types of compounds with S, Se, or Te: GaS , $GaSe$, or $GaTe$; and Ga_2S_3 , Ga_2Se_3 , and Ga_2Te_3 . The atomic arrangement in the first type of compound is such that the valence of gallium is +3, the same valence as the second type of compound.

Fission product barium as the metal or oxide forms a more stable sulfide, selenide, and telluride than gallium. However, neither the rare earth fission products nor ZrO_2 will remove the chalcogenides from gallium. Zirconium metal would react with Ga_2S_3 to form zirconium sulfide.

A.3.3 REACTIONS WITH GROUP V ELEMENTS

Gallium reacts with P, As, or Sb to form GaP , $GaAs$, or $GaSb$. Gallium arsenide is a common semiconductor material. These compounds will not form by reaction of P, As or Sb with Ga_2O_3 .

A.4 REFERENCES

1. *Encyclopedia of Chemical Technology*, Vol. 11, Wiley, New York, New York 1994.
2. J. C. Bailar, H. J. Emeleus, R. Nyholm, and A.F. Trotman-Dickenson, eds., *Comprehensive Inorganic Chemistry*, 1065-1093, Pergamon Press, Oxford 1973.

INTERNAL DISTRIBUTION

1. E. Beahm	26. G. T. Mays
2-6. T. M. Besmann	27. G. E. Michaels
7. B. B. Bevard	28. R. N. Morris
8. R. A. Bradley	29. R. T. Primm, III
9. S. L. Byerly	30. D. G. O'Connor
10. E. D. Collins	31. L. J. Ott
11. B. S. Cowell	32. R. R. Rahn
12. D. F. Craig	33. P. L. Rittenhouse
13. J. H. DeVan	34. J. D. Sease
14-16. J. R. DiStefano	35. D. J. Spellman
17. E. E. Duncan	36. C. C. Southmayd
18. E. C. Fox	37. K. R. Thoms
19. U. Gat	38. D. L. Williams, Jr.
20. R. G. Gilliland	39-48. D. F. Wilson
21. S. R. Greene	49. B. A. Worley
22. H. W. Hayden	50. Central Research Library
23. S. A. Hodge	51-52. ORNL Laboratory Records (OSTI)
24. L. L. Horton	53. ORNL Laboratory Records-RC
25. S. R. Martin, Jr., DOE/ORO	54. FMDP Library

EXTERNAL DISTRIBUTION

55. M. L. Adams, Armarillo National Resource Center for Plutonium, Department of Nuclear Engineering, Texas A&M University, College Station, TX 77843-3133.
56. D. Alberstein, Los Alamos National Laboratory, P. O. Box 1663, Los Alamos, NM 87545.
57. J. F. Baker, U.S. Department of Energy, MD-1, Forrestal Building, 1000 Independence Avenue SW, Washington, DC 20585.
58. T. Barr, U.S. Department of Energy, EPG, Argonne National Laboratory, 9800 South Cass Avenue, Argonne, IL 60439.
59. F. R. Best, Armarillo National Resource Center for Plutonium, Associate Professor, Department of Nuclear Engineering, Texas A&M University, College Station, TX 77843-3133.
60. J. J. Buksa, Los Alamos National Laboratory, P.O. Box 1663, MS-F628, Los Alamos, NM 87545.
61. D. P. Butt, Los Alamos National Laboratory, P. O. Box 1663, MS-F628, Los Alamos, NM 87545.
62. H. R. Canter, U.S. Department of Energy, MD-1, Forrestal Building, 1000 Independence Avenue SW, Washington, DC 20585.
63. A. I. Cygelman, U.S. Department of Energy, MD-3, Forrestal Building, 1000 Independence Avenue SW, Washington, DC 20585.
64. T. H. Gould, Jr., Lawrence Livermore National Laboratory, P. O. Box 808, MS-L186, Livermore, CA 94551
65. R. R. Hart, Armarillo National Resource Center for Plutonium, Associate Professor, Department of Nuclear Engineering, Texas A&M University, College Station, TX 77843-3133.
66. H. C. Irwin, Sandia National Laboratories, P. O. Box 969, MS-9015, Livermore, CA 94551
67. S. O'Kelly, Armarillo National Resource Center for Plutonium, Associate Professor, Department of Nuclear Engineering, Texas A&M University, College Station, TX 77843-3133.

68. D. J. Nulton, U.S. Department of Energy, MD-4, Forrestal Building, Room 6G-050, 1000 Independence Avenue SW, Washington, DC 20585.
69. D. Peko, U.S. Department of Energy, MD-3, Forrestal Building, Room 6G-050, 1000 Independence Avenue SW, Washington, DC 20585.
- 70-74. P. T. Rhoads, U.S. Department of Energy, MD-3, Forrestal Building, Room 6G-050, 1000 Independence Avenue SW, Washington, DC 20585.
75. J. M. Ryskamp, Idaho National Engineering and Environmental Laboratory, P. O. Box 1625, Idaho Falls, ID 83415-3885.
76. R. H. Steele, MPR Associates, Inc., 320 King Street, Alexandria, VA 22314-3238
77. G. B. Stevenson, U.S. Department of Energy, MD-4, Forrestal Building, Room 6G-050, 1000 Independence Avenue SW, Washington, DC 20585.
78. J. H. Thompson, U.S. Department of Energy, MD-4, Forrestal Building, Room 6G-050, 1000 Independence Avenue SW, Washington, DC 20585.

WWW DISTRIBUTION

The FMDP Web site, with a list of other relevant topical reports, is located at the following URL:

<http://www.ornl.gov/etd/FMDP/fmdpproc.htm>

M98054235

Report Number (14) ORNL/TM--13504

Publ. Date (11) 199710

Sponsor Code (18) DOE/~~MD~~MD, XF

UC Category (19) Uc-900, DOE/ER

19980720 089

DOE