Solution Processing of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Thin Films

CONF-971201--

A. Singhal*, M. Paranthaman*, E. D. Specht†, R. D. Hunt†, D. B. Beach*, P. M. Martin† and D. F. Lee†

*Chemical and Analytical Sciences Division, †Metals and Ceramic Division, ‡Chemical Technology Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee - 37831

RECEIVED

JUN 10 1998

O. R. N. L.

Abstract

The aim of this work was to develop a non-vacuum chemical deposition technique for $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ (YBCO) coated conductors on rolling-assisted biaxially textured substrates (RABiTS). We have chosen the metal-organic decomposition (MOD) and sol-gel precursor routes to grow textured YBCO films. In the MOD process, yttrium 2-ethylhexonate, barium neodecanoate, copper 2-ethylhexonate and toluene were used as the starting reagents. YBCO films processed by the MOD method on SrTiO_3 (100) single crystal substrates were consisted of c and a-axis oriented materials. These films also contained some amount of the random phase. The c and a-axis oriented materials were epitaxial on SrTiO_3 substrates. Films have a $T_{c,\text{onset}}$ of 89K and the best superconducting transition temperature of 63K. Films pyrolyzed at 525 °C and subsequently annealed at 780 °C in a $p(\text{O}_2)$ of 3.5×10^{-4} atm contained YBCO phase predominately in a-axis orientation. In the sol-gel route, yttrium-isopropoxide, barium metal, copper methoxide and 2-methoxyethanol were used as the starting reagents. Sol-gel YBCO films on SrTiO_3 substrates were epitaxial and c-axis oriented.

Introduction:

It has been observed that randomly oriented polycrystalline high-temperature superconducting (HTS) materials have poor critical current densities (J_c 's) $< 500 \text{ A/cm}^2$. On the other hand, oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ (YBCO) films grown epitaxially on single crystal oxide substrates, such as SrTiO_3 (100), exhibit J_c values $> 1 \text{ MA/cm}^2$ at 77K[1]. The aim of this work was to develop a non-vacuum chemical deposition technique for YBCO coated conductors on rolling-assisted biaxially textured substrate (RABiTS)[2]. The RABiTS approach developed at Oak Ridge gives a new approach for the fabrication of long lengths conductors for high temperature, high field applications.

We are presently using a metal-organic precursor route [3-7]. The most commonly used solution techniques may be grouped into three categories: (1) Sol-gel process that has 2-methoxyethanol as a reactant and solvent (2) hybrid processes that use chelating agents such as acetylacetonate or diethanolamine to reduce alkoxide reactivity and (3) metal-organic decomposition (MOD) technique that uses high molecular weight precursors, and water insensitive carboxylates, 2-ethylhexonates, etc. [8].

Recently several group of workers [4-6] have prepared high- J_c YBCO films on single crystal substrates using solution processing routes. McIntyre et al. used trifluoroacetate method to prepare YBCO superconducting films with T_c ($R = 0$) $> 92 \text{ K}$ and J_c ($T = 77 \text{ K}$, $H_{\text{app}} = 0$) $> 10^6 \text{ A/cm}^2$ in films of 70-80 nm nominal thickness [5]. In the present study, we focus on developing YBCO thin films on SrTiO_3 single crystal substrates using MOD and sol-gel precursor routes. The chemistry used in both precursor routes is different from the literature work.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Experimental Procedure:

The MOD precursor solution was prepared by mixing yttrium 2-ethylhexonate (STREM Chemicals, 98.5%), barium neodecanoate (STREM Chemicals, 95%) and copper 2-ethylhexonate (STREM Chemicals, 98.2%) in a molar ratio of 1: 2: 3, respectively. Solutions were heated to on hot plate ($< 100\text{ }^{\circ}\text{C}$) to prepare a homogenous solution but on cooling solution became very viscous. A solution suitable for spin coating was prepared by adding a small amount of 2-ethylhexonaic acid into this viscous precursor solution. The total cation concentration was 0.32 M . MOD solutions were spin coated on SrTiO_3 single crystals at 4000 rpm for 40 sec and heated in air for an hour at $275\text{ }^{\circ}\text{C}$ or $195\text{ }^{\circ}\text{C}$ at a rate of $2\text{ }^{\circ}\text{C}/\text{min}$. This procedure was repeated several times to adjust the thickness of the prefired films on the substrate. It has been found that the low temperature heating is an important step to achieve the continuous film. For example, films pyrolyzed rapidly at $500\text{ }^{\circ}\text{C}$ became discontinuous. These prefired films were heat treated at two different $p(\text{O}_2)$: 2×10^{-2} and 3.5×10^{-4} atm. Film A prepared at a $p(\text{O}_2)$ of 2×10^{-2} atm was heated at $450\text{ }^{\circ}\text{C}$ at a rate of $5\text{ }^{\circ}\text{C}/\text{min}$. while the film B synthesized at 3.5×10^{-4} atm was heated at $450\text{ }^{\circ}\text{C}$ at a rater of $15\text{ }^{\circ}\text{C}/\text{min}$ to burn off the carbon. Finally both films, A and B, were annealed at 870 and $800\text{ }^{\circ}\text{C}$, respectively, in different partial pressures of oxygens. Films were furnace cooled in 100% oxygen to $500\text{ }^{\circ}\text{C}$ and were oxygenated at this temperature for one hour and subsequently cooled down at a rate of $1\text{ }^{\circ}\text{C}/\text{min}$ to the room temperature.

Results and Discussion:

A. MOD Solution:

The DTA and TGA data were obtained on yttrium, barium and copper precursor powders in a $p(\text{O}_2)$ equal to 2×10^{-4} atm. The TGA scans are shown in Figure 1. All three precursors have

Figure 1: Thermal gravimetric analysis (TGA) plots of barium, copper and yttrium precursor materials in a $p(\text{O}_2)$ of 2.0×10^{-4} atm.

sharp thermal decomposition events. Copper precursor has two thermal events at 262.5 and 275 °C while yttrium and barium precursors have only single thermal events at 475 and 487.5 °C, respectively. The differences in thermal decomposition temperatures can cause inhomogeneities in films.

Figure 2 shows the XRD pattern for the film A ($t \approx 4000 \text{ \AA}$) formed on the SrTiO_3 (100) substrate by heating at 870 °C for 4 hours. This pattern exhibits YBCO as the predominant phase with small amounts of CuO and Y_2BaCuO_5 impurities. XRD pattern of film A shows both (001) and (h00) peaks of YBCO indicating the presence of both c and a-axis perpendicular orientations to the substrate and also some amount of random phase.

XRD results from the ω and ϕ scans for films grown on SrTiO_3 substrate revealed a (100) cubic texture. The full-width-at-half maximum (FWHM) values for YBCO films on SrTiO_3 substrates in case of c-axis orientation were 0.45° (out-of-plane epitaxy) and 0.5° (in-plane epitaxy). The typical phi scan for the (102) planes are shown in Figure 3. The FWHM value for in-plane crystallographic alignment of a-axis orientated material was 2° .

Figure 2: The room temperature powder X-ray diffraction pattern of YBCO films on (001) SrTiO_3 substrates.

As shown in Figure 4, scanning electron micrograph of film A surface that indicates the presence of a smooth microstructure. The microstructure is composed of YBCO platelets in both c and a-axis orientations. This microstructure also contain few secondary particles which are presumed to be primarily Y_2BaCuO_5 and CuO . Figure 5 shows the dc-resistance measurements on film A. The $T_{c, \text{onset}}$ is 88K while film became superconducting at 63K. XRD pattern (Figure 2) on film B ($t \approx 1 \mu\text{m}$) shows that this film has more YBCO in c-axis orientation in compared to the film A. The $T_{c, \text{onset}}$ of film B is 89K while the superconducting transition

Figure 3: A typical ϕ scan featuring the epitaxial nature of c-axis oriented YBCO films on SrTiO_3 substrates.

Figure 4: SEM photomicrograph of film A.

Figure 5: Temperature dependence of resistance for films A and B.

occurs at 63K as shown in Figure 5. To improve the surface finish of YBCO films processed at a $p(O_2)$ of 3.5×10^{-4} atm, it was decided that it might be better if films are heated to 525 °C to complete the decomposition of precursor materials (Figure 1) before annealing to high temperatures. Therefore, a film was heated to 525 °C at a rate of 15 °C/min and kept at that temperature for 20 min. after every coat. To avoid the carbon contamination in the film, films were heat treated in a 100% oxygen atmosphere at 525 °C for 8 hrs. One film was heated to 780 °C at a rate of 20-25 °C/min. in a $p(O_2)$ of 3.5×10^{-4} atm and hold it for 3 hours at that temperature. The film surface was shiny and smooth. XRD pattern of this film showed the YBCO phase present predominately in the a-axis orientation. The T_c of this film was only 46K. An another film was heated rapidly to 780 °C but YBCO phase still existed predominately in the a-axis orientation. This appears from these data that low temperature treatment (≤ 525 °C) to the film is important for the crystal structure and properties of YBCO films prepared from MOD precursors.

B. Sol-Gel Route:

YBCO films were also prepared by the alkoxide precursors. Copper methoxide (Alfa), barium metal (Alfa, 99.99%) , triethanolamine and 2-methoxyethanol (Alfa, Spectrometric grade) were used without further purification. The yttrium iso-propoxide was synthesized in our laboratory. The final YBCO precursor solution was prepared by mixing the yttrium and barium methoxyethanolate/ 2 – methoxyethanol solution with the copper methoxide/triethanolamine solution at the room temperature. A similar procedure has been used to prepare $TiBa_2Ca_2Cu_3O_{9-y}$ superconducting films [2]. The precursor solution was partially hydrolyzed for spin coating by adding approximately 1 equivalent of water per cation equivalent. The film was dried on the hot plate before the high temperature annealing. The film was first heat treated at 450 °C for 1.5 hrs and subsequently heated at 860 °C for 20 hrs in a $p(O_2)$ of 2×10^{-2} atm.

XRD pattern of this film is shown in Figure 6. The film is completely c-axis oriented and epitaxial. The typical phi scan for the (102) planes are shown in Figure 6 (inset). The FWHM values for sol-gel YBCO films on $SrTiO_3$ substrates were 0.45° (in-plane epitaxy) and 0.69° (out-of-plane epitaxy).

In summary, we have developed MOD and sol-gel solutions for preparing YBCO films. Films prepared on $SrTiO_3$ single crystals from MOD solutions have c and a-axis orientated YBCO phase. These films also contain some amount of the random phase. Although the c and a-axis oriented materials were epitaxial on $SrTiO_3$ single crystal substrates. On processing the film at a low $p(O_2)$ and at a lower-low temperature treatment, the amount of c-axis orientation increases. The $T_{c,onset}$ of films is 89K while the best superconducting transition temperature is 63K. The sol-gel YBCO films on $SrTiO_3$ single crystals were epitaxial and c-axis oriented.

Acknowledgements:

We are thankful to Dr. D. Kroeger and Dr. A. Goyal for their helpful discussions. The research was sponsored by the Divisions of Materials Sciences, Office of Basic Energy Sciences and Office of Energy Efficiency and Renewable Energy, Office of Utility Technology-Superconductivity Program. The research was performed at the Oak Ridge National Laboratory, ORNL, managed by Lockheed Martin Energy Research Corporation for the U.S. Department of

Energy under contract # DC-AC05-96OR22464. This work was partly supported by Oak Ridge Associated Universities, Oak Ridge, TN.

Figure 6: The X-ray powder diffraction pattern for the sol-gel YBCO film grown on a SrTiO_3 single crystal. The ϕ scan shows the epitaxial nature of c-axis oriented YBCO films on SrTiO_3 substrates (inset).

References:

1. J. M. Phillips, J. Appl. Phys., **79**, p. 1829 (1996).
2. A. Goyal, D. P. Norton, J. Budai, M. Paranthaman, E. D. Specht, D. M. Kroeger, D. K. Christen, Q. He, B. Saffin, F. A. List, D. F. Lee, P. M. Martin, C. E. Klabunde, E. Hatfield and V. K. Sikka, Appl. Phys. Lett., **69**, p. 1795 (1996).
3. N. Hirouki, S. Malcida, K. Takeshi, I. Yoshikazu, I. Takshi and O. Yukio, Chemistry Letters, p. 2403 (1987).
4. T. Manabe, W. Kondo, S. Mizuta and T. Kumagi, Jap. J. Appl. Phys., **30**(9B), p. L1641 (1991).
5. P. C. McIntyre, M. J. Cima and A. Roshko, J. Appl. Phys., **77**(10), p. 5263 (1992).
6. M. W. Rupich, Y. P. Lin and J. Ibechem, Appl. Phys. Lett., **60**(11), p. 1384 (1992).
7. M. Paranthaman and D. B. Beach, J. Am. Ceram. Soc., **78** (9), p. 2551 (1995).
8. M. Paranthaman, S. S. Shoup, D. B. Beach, R. K. Williams and E. D. Specht, Mater. Res. Bull., **32** (12), p. 1697 (1997).

M98005654

Report Number (14) ORNL/CP--98102
CONF-971201
_____
_____

Publ. Date (11) 199712

Sponsor Code (18) DOE/ER, XF

UC Category (19) UC-400, DOE/ER

19980702 044

DTIC QUALITY INSPECTED 1

DOE