QUARTERLY TECHNICAL REPORT

Attachment I: Progress at IPST DE-FC36-996010379

In the last few months, we studied the adsorption of cationic pressure sensitive adhesive (PSA) on wood fiber, and the buildup of PSA in a closed water system during paper recycling. The results are presented here.

1. Experimental

Adsorption

Two-mil thickness of cationic PSA (charge content 15%) was applied on Silicon Release Liner, dried at 90 °C for 3 mins, and then transferred to office white paper. The final PSA content was adjusted to desired amount (range from 0.5% to 8% based on oven dried paper). The paper was tore to small pieces and soaked in water (pH8.0) with 1% consistency for 4 hours. The mixture was disintegrated for 20,000 revolutions in the standard disintegrator with the propeller operating at 3,000 rpm in the stock. After standing for 4 hours, the stock was centrifuged at 3000 rpm for half an hour. The content of PSA in the supernatant clear solution was measured by colloidal titration. The PSA content was also measured by UV spectroscopy, but the results were unreliable because contaminants in the paper interfere the adsorption of PSA.

PSA accumulation

PSA accumulation in a closed water system during paper recycling was studied as the follows. The pulp stock of 4% consistency with 1% PSA based on oven dried paper was made according to the above procedure. After standing for one hour, the stock was filtered through a 150 microns screen. 50 ml of filtrate was collected and the rest filtrate was used for the next step pulping. In every step, about 20 percent of fresh water is needed to compensate the water lose in the last step. Water from another pulping process without PSA was collected as reference. The PSA content in the filtrate was measured according to the above procedure.

2. Results and discussion.

Adsorption

The results of the PSA adsorption on the pulp of office copy paper are listed in Table 1 and Figure 1. It can be seen that when PSA content is less than 4%, more than 90% of PSA will be adsorbed on the fiber. Adsorption equilibrium could not be reached even when the PSA content reaches 8%.

Table 1. PSA adsorption on the pulp of office copy paper

PSA content (%)	0.5	1	2	3	4	5	8
Adsorption percentage (%)	97.4	91.0	92.4	94.7	91.2	85.0	80.0

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Figure 1. Adsorption isotherms of PSA on the wood fiber of office copy paper

PSA accumulation

The PSA accumulation in the pulping water is shown in Figure 2. After 8 pulping cycles, the PSA concentration in the pulping water is 0.052 g/L. With 1% PSA in the office paper and pulping consistency of 4%, the PSA concentration in the water would be 0.4 g/L if no PSA adsorption on the fibers. This suggests that significant

amount of novel PSA was adsorbed on the fiber surfaces.

Figure 2. PSA accumulation in the closed pulping water system

Because different contaminants in the paper also accumulated in the recycled water, the colloidal titration method may lead to a misunderstanding. Fluorescent spectroscopy method will be considered for future studies.

3. Conclusions

More than 90% of PSA could be adsorbed on to fiber when the PSA content is less than 4%. The adsorption does

not reach equilibrium with PSA content up to 8%. After 8 cycles, the PSA content in the water reaches 52 mg/L with total PSA content above 400 mg/L in a 4% pulp. Further studies are needed.

Attachment II: Progress at Georgia Tech.

We started the project in April 1999. In the past half a year, we tried to develop an environmentally- friendly polymerization process to synthesize a novel re-dispersible PSA by co-polymerizing an oil-soluble monomer (butyl acrylate, BA) and a cationic monomer MAEPTAC. The following are some important results.

1. Semi-batch emulsion co-polymerization

1.1 Basic recipe

H2O	BA	VA-044	CTAB	Co-monomer
118.42 g	75 g	0.0005 M/L H2O	1% wt BA	variable

1.2 Process

Stage one: batch homo-polymerization

Part the of ingredients except MAEPTAC are added at the beginning of the polymerization. Polymerization begins as soon as the initiator is added and the temperature is increased. The stage one will last one hour or so.

Stage two: semi-batch co-polymerization

The residual of ingredients including all of the MAEPTAC is added continuously by the way of emulsion addition.

Stage three: post polymerization

1.3 Results

It was shown that semi-batch emulsion co-polymerization does not work in copolymerizing BA and MAEPTAC. It is suggested that MAEPTAC is so hydrophilic that the free radicals formed in the aqueous phase do not enter into the particles.

2. Copolymerization with a special redox initiator system

2.1 Basic recipe

Component	Amount (g)
d-H2O	118
Washed BA	75
CHP	2.25 (3% BA)
TEPA	2.56 (moles equal to CHP)
70% Triton X-405	6.43
NaCl	3.66 g or No
MAEPTAC	Variable

2.2 Results

The recipe above includes a redox initiation system in which the oxidant (cumene hydroperoxide or CHP) is in the monomer phase, while the reductant (tetraethylenepentamine or TEPA) is in the water phase. This promotes interfacial polymerization, and consequently, incorporation of both the oil-soluble BA and the water-soluble MAEPTAC. We studied the influence of the polymerization method, salts

and MAEPTAC level on the copolymerized efficiency. The results are listed in Tables 1-3. It was found that miniemulsion polymerization is a more effective polymerization method to copolymerize BA and MAEPTAC than macroemulsion polymerization. This is due to the fact that, in a macroemulsion, the oil-soluble CHP has difficulty getting from the monomer droplets to the site of polymerization in the polymer particles. In miniemulsion polymerization, the monomer droplets are nucleated, and therefore no transport of CHP is required. The salt has a two-fold influence. On one hand, the copolymerization efficiency is reduced by the presence of salt. On the other hand, the final conversion increases. From Table 3, it is found that the negative effect on the copolymerization efficiency could be offset by the MAEPTAC. With increase of MAEPTAC feeding concentration, the copolymerized efficiency rapidly increase up to one.

Table 1 Comparison of macroemulsion and miniemulsion polymerization without salts

	Conversion, %	Polymer composition, wt%	Copolymerized efficiency*
Macroemulsion Polymerization	80	6.82	0.58
Miniemulsion polymerization	100	7.27	0.78

*Copolymerized efficiency is defined as the ratio of the incorporated MAEPTAC to the feeding MAEPTAC.

Table 2 The effects of salts

	Conversion, %	Polymer composition wt%	Copolymerized efficiency
No salts	100	7.27	0.78
0.53 M NaCl	100	4.58	0.48

Table 3 The effects of MAEPTAC level with 0.53M NaCl

MAEPTAC feeding concentration, wt%	Conversion, %	Polymer composition wt%	Copolymerized efficiency
9.1	100	4.58	0.48
13.0	100	11.54	0.87
16.7	100	~17	~1.00

Conclusions: Miniemulsion polymerization with a special two-component redox initiator system: one hydrophobic, the other one hydrophilic in the presence of salts is very effective to copolymerize BA and MAEPTAC.

Progress at University of Georgia at Athens

The project is focused on the synthesis of water-soluble and easily removable cationic polymer pressure sensitive adhesives (PSAs). Because the fund from DOE was not available until March 1999, the actual work at UGA did not start until April 1999. According to early proposal, UGA will mostly focus on the PSA physical property tests. During the last two months, the following works have accomplished at UGA:

- Literature search
- laboratory preparation, including chemicals and glassware purchase
- Test equipment was purchased and installed;
- Some PSA samples made at IPST have been characterized at UGA to determine chemical composition, polymer structure, and molecular weight;
- Preliminary investigation of PSAs synthesis has been carried out.

The detail results, existing problems and some preliminary discussion were given below.

I. The Physical Properties for those samples synthesized in ISPT

1. Solubility of PSA samples

All the samples with different cationic charger contents (from 5%-20%) are all soluble well in DMF, DMSO, THF and chloroform.

2. The molar ratios of monomers in PSA samples as determined with NMR

The compositions of all eight PSA samples were examined with ^1H -NMR (Mercury 300MHz, CD_3Cl as solvent). According to the integrate area ratio of peaks around 4.0ppm and 3.4ppm, which are corresponding to $-\text{OCH}_2-$ of butyl acrylate and $-\text{N}^+(\text{CH}_3)_3$ of MAPTAC respectively, we could calculate out the molar ratios of two monomers BA and MAPTAC in the copolymers. The results are listed in table 1.

Table 1. The molar ratios of PSA copolymers

Samples Name	MAPTAC/BA fed ratio		Calculated ratio	
	Molar Ratio	MAPTAC percentage	Molar Ratio	MAPTAC percentage
MB5	5.25:100	5%	6.0:100	5.7%
MB10	11.0:100	10%	11.8:100	10.6%
MB15	17.5:100	15%	18.0:100	15.2%
MB20	25.0:100	20%	26.5:100	20.9%
MB15a	17.5:100	15%	20.0:100	16.7%
MB15b	17.5:100	15%	18.6:100	15.7%
MB15z	17.5:100	15%	18.3:100	15.5%
MBE15	17.5:100	15%	21.4:100	17.6%

We can see from the table 1 that the actual molar ratios of two monomers in PSA copolymers are close to the fed ratio. However, we cannot conclude that the reactivity of two monomers is the same because the composition of the copolymers can change with the polymerization conditions.

3. Maldi

Several PSA samples were sent to Dr. Dennis Philips, who is a Mass spectroscopy expert and director for management of Mass spectrometers in Department of Chemistry/UGA, for molecular weight determination by Maldi (Matrix-assisted laser desorption/ionization). Unfortunately, no peaks were found above 2 thousands. Therefore, it is difficult for using Maldi to determine the molecular weight for cationic polymers.

4. The dn/dc

We also tried to use light scattering instrument to determine the molecular weight of PSA samples. To use lightscattering, dn/dc of the copolymers must be measured first. Table 2 was the dn/dc values for the samples in DMF. The detector was Waters 401 Differential Refractometer with sensitive set at 32, calibration constants was $1.5150\text{e-}4$ as calibrated by using NaCl aqueous solution.

Table 2 The dn/dc of PSA samples in DMF

Samples Name	MAPTAC content	dn/dc
MB5	5.7%	0.0452
MB10	10.6%	0.0511
MB15	15.2%	0.0626
MB20	20.9%	0.0658
MB15a	16.7%	0.0519
MB15b	15.7%	0.0581
MB15z	15.5%	0.0610
MBE15	17.6%	0.0678

As shown in table 2, dn/dc of the copolymers increases with the MAPTAC ratio increased from 5% to 20%. This trend was shown clearly in Fig. 2. The dn/dc of MBE15 is much larger than that of copolymers with the same MAPTAC probably due to its crosslinked structure.

5. The molecular weight

We tried to use two different methods to measure the molecular weights:

(1) Batch mode

Using Dawn DSP laser photometer (Wyatt Technology Co.) as detector, DMF as solvent and Astra4.7 software to draw Zimm plot and calculate the molecular weight. The result was collected in Table 3. For example, fig.3 was Zimm plot of sample MB15b.

Table 3 Molecular weight of PSA samples as determined by batch mode

Samples Name	Molar Mass (X 10 ⁻⁴)
MB5	1.417
MB10	1.205
MB15	1.957
MB20	1.348
MB15a	1.977
MB15b	1.591
MB15z	1.469
MBE15	2.786

2) GPC-LS (with column)

The batch mode can only measure molecular weight. In order to determine molecular distribution, GPC system has to be connected with Dawn DSP laser light scattering system. We spent a lot of time on it, but unfortunately the results are unreasonable and we have to carefully study the instrument system again. Because we do not have general GPC software, we can not get the relative molecular weight either.

6. FT-Raman

Theoretically, FT-Raman can be used in quantitative analysis. However, the literatures in this field are quite few. We are trying using it to monitor polymerization process. The results will be given in the next report.

II. The preliminarily investigation of PSA synthesis

1. Materials preparation

All chemicals are purchased from Aldrich Co.

Butyl acrylate (BA), ethylene glycol dimethylacrylate (EGDM) were washed several times with 5% NaOH aqueous solution then several times with distilled water to remove inhibitors. Dried thoroughly with anhydrous sodium sulfate and filtered.

AIBN was used as received.

[3-(Methacryloylamino)propyl]trimethylammonium chloride (MAPTAC, 50% in water) was washed five times with ethyl ether to remove inhibitors. The residue was driven off by a rotary evaporator. The volume was adjusted to the same as before extraction, i.e. the concentration of MAPTAC is still supposed to be 50%).

We also tried to purify MAPTAC as described below: MAPTAC aqueous solution was washed three times with ethyl ether and further extracted with acetone for many times until the solution became sticky. Then the residue was dried by water/oil vacuum pump to remove acetone and water. However, the result amorphous solid was only partially dissolved in water. It was believed that the monomers are partially polymerized during the purification. The method for purifying the monomer need to be further studied.

2. Polymerization

Polymerization was carried out for practice according to the procedures described by IPST. No further studies were performed.