TITLE: *IN SITU* INFRARED STUDY OF CATALYTIC DECOMPOSITION OF NO

REPORT TYPE: Semiannual Technical Progress Report

REPORTING PERIOD: February 1, 1998 to August 1, 1998

PRINCIPAL AUTHOR(s): Steven S.C. Chuang, Khalid Almusaiter and Ram
Krishnamurthy

ISSUED REPORT DATE: August 18, 1998

INSTITUTION: The University of Akron
Department of Chemical Engineering
Akron, Ohio 44325-3906
(330) 972-6993

DOE AWARD NUMBER: DE-FG22-95PC95224 -06

Disclaimer

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Abstract

The growing concerns for the environment and increasingly stringent standards for NO emission have presented a major challenge to control NO emissions from electric utility plants and automobiles. Catalytic decomposition of NO is the most attractive approach for the control of NO emission for its simplicity. Successful development of an effective catalyst for NO decomposition will greatly decrease the equipment and operation cost of NO control. Due to lack of understanding of the mechanism of NO decomposition, efforts on the search of an effective catalyst have been unsuccessful.

Scientific development of an effective catalyst requires fundamental understanding of the nature of active site, the rate-limiting step, and an approach to prolong the life of the catalyst. Research is proposed to study the reactivity of adsorbates for the direct NO decomposition and to investigate the feasibility of two novel approaches for improving catalyst activity and resistance to sintering. The first approach is the use of silanation to stabilize metal crystallites and supports for Cu-ZSM-5 and promoted Pt catalysts; the second is utilization of oxygen spillover and desorption to enhance NO decomposition activity. An innovative infrared reactor system will be used to observe and determine the dynamic behavior and the reactivity of adsorbates during NO decomposition, oxygen spillover, and silanation. A series of experiments including X-ray diffraction, temperature programmed desorption, temperature programmed reaction, X-ray photoelectron spectroscopy will be used to characterize the catalysts. The information obtained from this study will provide a scientific basis for developing an effective catalyst for the NO decomposition under practical flue gas conditions.

Table of Contents

	Page
Title Page	1
Disclaimer	2
Abstract	3
Table of Contents	4
List of Graphical Materials	5
Executive Summary	6
Introduction	7
Results.	8
Discussion	12

List of Graphical Materials

- Figure 1 (a) MS analysis of IR reactor effluent during the step switch from He ($30 \text{ cm}^3/\text{min}$) to 1% NO ($30 \text{ cm}^3/\text{min}$). (b) IR Intensity of adsorbates versus time, on Rh/ Al_2O_3 (125 mg) at 673 K.
- Figure 2 IR spectra of adsorbates during the step switch from He ($30 \text{ cm}^3/\text{min}$) to 1% NO ($30 \text{ cm}^3/\text{min}$) on Rh/ Al_2O_3 at 673 K.
- Figure 3 (a) MS analysis of IR reactor effluent during the step switch from He ($20 \text{ cm}^3/\text{min}$) to 1% NO ($20 \text{ cm}^3/\text{min}$). (b) IR Intensity of adsorbates versus time, on Rh/C (100 mg) at 673 K.
- Figure 4 IR spectra of adsorbates during the step switch from He ($20 \text{ cm}^3/\text{min}$) to 1% NO ($20 \text{ cm}^3/\text{min}$) on Rh/C at 673 K.
- Figure 5 (a) MS analysis of IR reactor effluent during the step switch from He ($30 \text{ cm}^3/\text{min}$) to 1% NO ($30 \text{ cm}^3/\text{min}$). (b) IR Intensity of adsorbates versus time, on Pd/ Al_2O_3 (125 mg) at 673 K.
- Figure 6 IR spectra of adsorbates during the step switch from He ($30 \text{ cm}^3/\text{min}$) to 1% NO ($30 \text{ cm}^3/\text{min}$) on Pd/ Al_2O_3 at 673 K.
- Figure 7 (a) MS analysis of IR reactor effluent during the step switch from He ($20 \text{ cm}^3/\text{min}$) to 1% NO ($20 \text{ cm}^3/\text{min}$). (b) IR Intensity of adsorbates versus time, on Pd/C (100 mg) at 673 K.
- Figure 8 IR spectra of adsorbates during the step switch from He ($20 \text{ cm}^3/\text{min}$) to 1% NO ($20 \text{ cm}^3/\text{min}$) on Pd/C at 673 K.

Executive Summary

During the sixth semi-annual period, *in situ* infrared (IR) coupled with mass spectroscopy (MS) was successfully applied to investigate the direct catalytic decomposition of NO over carbon supported-Rh and Pd catalysts. NO decomposition on these catalysts initially produced N₂ and adsorbed oxygen. Different catalysts exhibit different capability for manipulating adsorbed oxygen. Rh/Al₂O₃ shows little activity for oxygen desorption, resulting in loss of catalyst activity; Rh/C shows the ability for promoting the adsorbed oxygen-carbon reaction, removing oxygen in the form of CO₂; Pd/Al₂O₃ shows some activity for O₂ desorption. Use of carbon as a support for Pd promotes O₂ desorption, resulting in improvement of NO decomposition activity. The *in situ* IR results provide evidence to support the behavior of adsorbed oxygen on carbon-supported Rh and Pd catalysts.

***In Situ* Infrared Study of Catalytic Decomposition of NO On Carbon-Supported Rh and Pd Catalysts**

Introduction

NO is a major pollutant in the exhaust of various combustion processes. The growing concerns for the environment have resulted in increasingly stringent NO emission standards [1-3]. Removal of NO from the exhaust streams of automobiles, power plants, and other combustion processes has become a challenging task.

Depending on the nature of the combustion process, various approaches for NO removal have been developed. The catalytic approaches for the removal of NO include (i) the reaction of NO with CO [1-4], (ii) selective catalytic reduction with NH_3 and hydrocarbons [5,6], and (iii) the direct decomposition of nitric oxide [7-10]. The advantages and disadvantages of each approach are listed in Table 1.

The direct decomposition of NO, $2\text{NO} \rightarrow \text{N}_2 + \text{O}_2$, is the most attractive approach for NO removal because of its simplicity [7]. It is thermodynamically favorable at temperatures below 2000 K. For the NO decomposition catalyst development, the two critical issues to be addressed are catalyst activity and durability [11].

Studies on the proposed elementary steps for NO decomposition have revealed that the low activity of the catalysts is due to their inability to desorb oxygen produced from NO dissociation [8,10]. Oxygen from dissociated NO is strongly bonded to the catalyst surface, poisoning NO dissociation sites and inhibiting further NO dissociation. Various approaches to remove adsorbed oxygen from the NO dissociation sites include: (i) thermal desorption, (ii) autoreduction of the surface in He flow [8], and (iii) spillover of adsorbed oxygen [10]. One possible approach is to use carbon as a support for the catalyst system, facilitating the removal of

oxygen by the formation of CO₂. Recent studies have shown that activated carbon has the capability to reduce NO to form N₂ and CO₂ [12-14]. Near 100% conversions of NO were achieved using a Ni or Co catalyst supported on activated carbon at temperatures above 713 K. The NO conversions on carbon supported catalysts decreased in the presence of O₂ [15].

Rhodium (Rh) and Palladium (Pd), the major components in three way catalytic converters, have shown excellent activity for the dissociation of adsorbed NO. To determine the feasibility of using carbon for removal of adsorbed oxygen on Rh and Pd, we have examined the activity of carbon- and Al₂O₃-supported Rh and Pd catalysts and the nature of the adsorbate for the NO decomposition reaction. We have found that carbon promotes the N₂ and CO₂ formation over Rh catalyst while enhancing N₂ and O₂ formation on Pd catalyst.

Results

The 2 wt% Rh/Al₂O₃, 2 wt% Rh/C, 2 wt% Pd/ Al₂O₃, and 2 wt% Pd/C catalysts were prepared by incipient wetness impregnation technique of large surface area γ - Al₂O₃ (Alfa Products, 100 m²/g surface area) and carbon (activated carbon, Ambersorb 563, Rohm & Haas, 550 m²/g surface area) with RhCl₃ or PdCl₂ solutions. The ratio of the volume of the solution to the weight of the support used in the impregnation step was 1 cm³ to 1 g. The catalysts were dried overnight in air at 303 K. They were then calcined in air at 673 K for 8 h and reduced in flowing H₂ at 673 K for 8 h. The catalysts prepared were characterized by X-Ray Diffraction (XRD) and the crystallite size was determined. The crystallite sizes of Rh in Rh/Al₂O₃ and Pd in Pd/Al₂O₃ were found to be 50 Å and 64 Å, respectively. The crystallite sizes of Rh in Rh/C and Pd in Pd/C were found to be 47 Å and 70 Å, respectively.

Al₂O₃-supported catalysts were pressed in the form of self-supporting disks (40 mg each); one of the disks was placed in the infrared (IR) cell for *in situ* transmission IR studies and the

other two disks were broken down into flakes and placed in the exit line of the IR reactor cell [16]. The additional catalyst disks were used to increase the amount of desorbing species and conversions to obtain a strong signal in the Mass Spectrometer (MS). Carbon-supported catalysts were diluted with KBr (catalyst: KBr = 1:10) and 20 mg of the solid mixture was placed in the Diffuse Reflectance Infrared Fourier Transform (DRIFT) cell in powder form for *in situ* IR studies. Additional carbon supported catalyst (90 mg) was placed in a tubular reactor, which was connected in series with the DRIFT cell.

The catalysts were reduced *in situ* in flowing H_2 at 673 K for 1 h. Following the *in situ* reduction of the catalyst, the NO decomposition study was carried out at 673 K. The catalyst was exposed initially to He flow. A 4-port valve was used to switch the He flow to 1% NO in He flow in a step mode. This NO step switch technique allows investigating the sequence of adsorbate and product formation during the NO decomposition reaction on the catalyst surface. Fourier Transform Infrared Spectroscopy (FTIR) was used to monitor the adsorbate concentrations and MS to analyze the change in the concentration of the gaseous product from the effluent of the IR reactor cell.

NO decomposition on Rh/Al₂O₃

Fig. 1a shows the MS analysis of the IR reactor cell effluent during the 1% NO step switch reaction studies on Rh/Al₂O₃ at 673 K. The IR spectra of the adsorbates corresponding to the MS profiles are shown in Fig. 2. To determine the role of adsorbates in the reaction, the variation in the IR intensity of major adsorbates was plotted versus time in Fig. 1b. Absence of adsorbed species prior to the step switch indicates that the catalyst surface was clean. The step switch from He to 1% NO at time=0 resulted in the formation of N₂. The absence of NO in the

initial period is a result of near 100% conversion. Ar, the species added in 1% NO flow, shows that a near perfect step switch was achieved. A close examination of MS and IR intensity profiles in Fig. 1a and b revealed that the NO step switch reaction may be divided into three stages. Stage 1 comprises of nearly complete NO conversions on the reduced metal surface resulting in the depletion of all the NO adsorbates in the 0-10 min period; stage 2 is the emergence of NO adsorbates in the 10-31 min period; and stage 3 is the appearance and slow growth of gaseous NO profile after 31 min. The wavering behavior of the MS profile of N₂ during stage 1 and 2 suggests the unsteady behavior of the following reaction:

Reaction (1) is a global reaction and its elementary steps will be discussed later.

During stage 2, Rh-NO⁺ at 1893 cm⁻¹, Rh⁰-NO⁻ at 1644 cm⁻¹, nitrate ion at 1361 cm⁻¹ and bridging bidentate at 1540 cm⁻¹ began to develop at 11 min as a result of modification of Rh surface by adsorbed oxygen, i.e., Rh-O. Rh-O slowly converts the reduced Rh sites to Rh⁺ sites, which chemisorb NO as Rh-NO⁺. Fig. 1a shows that as the Rh-NO⁺ intensity approached to 90% of its saturated level, gaseous NO emerged at stage 3 indicating the loss of catalyst activity. The loss of NO decomposition activity allows populating of non-dissociated NO on the surface, such as Rh⁰-NO⁻ and Rh-NO⁺. Rh⁰-NO⁻ and Rh-NO⁺ may react with adsorbed N, already existing on the surface, resulting in N₂O formation. The formation of N₂O from adsorbed N and adsorbed NO is further supported by the crossover between the decrease in the N₂ profile and the increase in the NO profile as shown in Fig.1a.

NO decomposition on Rh/C

Fig. 3a shows the MS analysis of the IR reactor cell effluent during the 1% NO step switch reaction studies on Rh/C at 673 K. The IR spectra of the adsorbates corresponding to the

MS profiles are shown in Fig. 4. The step switch from He to 1% NO resulted in 100% conversion of NO and the formation of N_2 during the first 50 min of the reaction. The step switch also caused the development of the adsorbates at 1400, 1277, 1151 and 1101 cm^{-1} and approached saturation at 20 min as shown in Figs. 3b and 4. The band at 1400 cm^{-1} has been assigned to oxygen species on carbon surface in the form of esters, phenols or carbonates [17,18]. The band at 1277 cm^{-1} could also be due to oxygen species on the surface, resulting from C-O stretches in species like aromatic ethers. The bands at 1151 and 1101 cm^{-1} were assigned to the C-N species on the surface [19]. The assignment of these species was further verified by IR studies of O_2 and N_2 adsorption on carbon supported catalysts surface [20].

Comparison of the results in Figs. 1 and 3 shows that the NO reaction on Rh/C differed from that on Rh/ Al_2O_3 in the development and formation of both adsorbates and products. The major products on Rh/C are N_2 and CO_2 . CO_2 emerged at the moment when the C-O species at 1402 cm^{-1} showed a drastic increase in its intensity. The result suggests that the C-O species is a precursor toward the CO_2 formation.

NO decomposition on Pd/ Al_2O_3

Fig. 5a shows the MS analysis of the IR reactor cell effluent during the 1% NO step switch reaction studies on Pd/ Al_2O_3 at 673 K. The IR spectra of the adsorbates corresponding to the MS profiles are shown in Fig. 6. Like the reaction on Rh/ Al_2O_3 , the NO decomposition process on Pd/ Al_2O_3 can be divided into three stages. Stage 1 is near complete conversions of NO; stage 2 is the NO adsorbate development; and stage 3 is the emergence of NO and O_2 . The major difference between Pd/ Al_2O_3 and Rh/ Al_2O_3 is that Pd/ Al_2O_3 catalyzes significant amount of O_2 .

The development of Pd-NO⁺ at 1802 cm⁻¹ at 2.9 min in stage 2 reflects an increase in the concentration of Pd⁺ produced by adsorbed oxygen from NO dissociation. As the intensity of Pd-NO⁺ reached a constant level as shown in Fig. 5b, gaseous NO and O₂ emerged while the reaction process moved to stage 3.

NO decomposition on Pd/C

Fig. 7a shows the MS analysis of the reactor effluent during the 1% NO step switch reaction studies on Pd/C at 673 K. The IR spectra of the adsorbates corresponding to the MS profiles are shown in Fig. 8. The step switch to 1% NO resulted in near 100% conversions of NO and the formation on N₂, during 52 min of the reaction. The development of Pd-NO⁺ at 1770 cm⁻¹, C=O at 1655 cm⁻¹ [12,18], C-O at 1398 cm⁻¹ and C-N at 1132 cm⁻¹ was also observed. The appearance of Pd-NO⁺ reflects an increase in the concentration of Pd⁺ produced by adsorbed oxygen from NO dissociation. As in Pd/Al₂O₃, a significant amount of O₂ was produced with the emergence of gaseous NO. Comparison of the results of Rh/C in Fig.3a and Pd/C in Fig. 7a, reveals that Rh/C catalyzes the formation of CO₂, but Pd/C catalyzes the formation of O₂.

Discussion

Table 2 shows the activity and selectivity of the different catalysts for the NO decomposition. The amount of oxygen adsorbed from, 2NO + 2S → N₂ + 2O-S, was normalized by catalyst weight. It can be inferred from Table 2 that the carbon-supported catalysts have the ability to uptake more oxygen than alumina supported catalysts. Comparison of the amount of adsorbed oxygen with the number of metal surface atoms (Table 2) reveals that the oxygen adsorbed on the surface diffuses to the bulk causing the formation of bulk oxides.

The behavior of the catalyst (i.e. activity, selectivity and adsorbates on the catalyst surface) may be interpreted using the proposed mechanism listed in Table 3. Formation of

different products can be explained by the structure of adsorbates and their reaction pathways on the catalyst surface. Prior to the emergence of gaseous NO (i.e. stage 1), instantaneous dissociation of adsorbed NO (step 2 in Table 3) takes place on both Pd⁰ and Rh⁰ surfaces of the Al₂O₃ supported catalysts. Facile nature of the NO dissociation allows the immediate formation of N₂ (step 3) and near 100% conversions of NO on the catalyst surface. Absence of steric crowding of adsorbed NO molecules on the catalyst surface is attributed to the facileness of step 2. The instantaneous consumption of the precursor adsorbates for the NO dissociation yielded no adsorbate IR bands, preventing verification of the nature of the NO adsorbate in step 2.

Our previous transient studies have revealed that Rh⁰-NO⁻ at 1644 cm⁻¹ and Pd⁰-NO at 1745 cm⁻¹ are the active adsorbates for NO dissociation to form adsorbed N and adsorbed O during the NO-CO reaction [21,22]. It is expected that the same adsorbates may decompose in the absence of CO and serve as the active adsorbates for NO decomposition. For Rh/Al₂O₃ catalyst, Rh-NO⁺ was not the active adsorbate for NO dissociation. As it approached the saturated level, Rh/Al₂O₃ began losing its activity for NO decomposition. The same trend was observed for Pd-NO⁺ and NO conversion activity over Pd/Al₂O₃.

The formation of N₂O (step 5) requires both adsorbed N and adsorbed NO. Our previous studies have shown this step takes place on the reduced metal sites [21]. Although different amounts of N₂O were produced on these four catalysts, all the N₂O formation occurred near the crossover point where the N₂ profile decreased and the NO profile increased. The results indicate that N₂O formed at the optimum concentration of adsorbed N and adsorbed NO.

The lack of oxygen formation (step 6) during the 100% NO conversion (i.e. stage 1 on these four catalysts) suggests that the NO conversion to N₂ at this stage is not a catalytic process instead it is a stoichiometric reaction as shown in reaction (1). A process is defined catalytic

when active sites are regenerated and the product formation is continuous. The absence of oxygen desorption during the high NO conversion is further evidenced by the absence of NO₂ formation (step 7). It has been well established that NO₂ can be formed from either step 7 or gas phase reaction of NO with O₂. The observations of the present study agreed well with several studies, which have suggested that adsorbed O (i.e., S-O, where S is Rh or Pd) remains on the surface [10,23,24]. Unless the catalyst has the ability to desorb oxygen, S-O from reaction (1) will accumulate on the surface and blocks the sites for NO dissociation resulting in the increase in the surface coverage of the IR-observable species (active and spectator adsorbate).

Interestingly, each of these four different catalysts exhibits different abilities to manipulate adsorbed oxygen. Rh/Al₂O₃ shows the weakest oxygen desorption capability, letting majority of oxygen to be accumulated on the Rh surface and losing NO decomposition activity. The Rh/C catalyst exhibits the ability of spilling over the adsorbed O from Rh surface onto the carbon support and reacting with carbon to produce CO₂ as in step 8 (i.e., gasification of the carbon). Production of CO₂ in Fig. 3a appears to result from migration of adsorbed oxygen onto the carbon surface to form the C-O species at 1277 and 1402 cm⁻¹ as seen in Fig. 4. Rh/C catalyst eventually lost its activity for CO₂ formation, indicating that step 8 was interrupted. The loss of Rh/C activity for CO₂ formation is not surprising. As the carbon, located near the interface of Rh metal and carbon support, is being removed by CO₂ formation, the Rh metal and carbon surface are expected to undergo dramatic modifications causing either decreasing Rh-C interface or losing the contact between Rh and carbon. SEM studies have shown that NO reaction with carbon causes pitting [15].

Absence of step 8, CO₂ formation, on Pd/C is in good agreement with the literature observations [25]. Pd shows the ability to desorb oxygen after saturation is reached as observed

in Pd/Al₂O₃ and Pd/C. The difference in the activity of the Rh/C and Pd/C catalysts towards desorption of oxygen could be due to the difference in the binding energy of oxygen to Rh (145 kcal/mol) and to Pd (87 kcal/mol) [26,27]. Thus, it may be easier for adsorbed oxygen on Pd to recombine for desorption as molecular oxygen. The difference in Pd/C and Pd/Al₂O₃ in oxygen desorption could be due to dispersion of metal particles (Table 2) or metal-support interaction. Lack of detailed structural surface information does not allow elucidation of the role of metal-support interaction in the oxygen desorption.

As discussed earlier, the difference in the activity and selectivity of these four catalysts for the NO decomposition and reaction can be attributed to the difference in their capability to activate each elementary step listed in Table 3. The facile nature of NO dissociation (step 2) and N₂ formation (step 3) points to steps 6 and 8 as the rate limiting steps for the overall reaction. Rh promotes step 8 for CO₂ formation while Pd activates the step 6 for O₂ formation on the carbon based catalysts. The rate of these steps, temperature-dependent, are clearly not fast enough compared to NO dissociation (step 2) resulting in the accumulation of adsorbed oxygen and then loss of the catalyst activity. We have also studied the reaction on Rh/Al₂O₃ and Pd/Al₂O₃ at 573 K. Decreasing the temperature from 673 to 573 K resulted in shortening the time for near 100% NO conversion (i.e. stage 1) for Rh/Al₂O₃ from 31 to 19 min and for Pd/Al₂O₃ from 20 to 14 min. Increasing the reaction temperature on Rh/C and Pd/C to 773 K resulted in extending the activity for near 100 % conversion for Rh/C from 51 to 4 h and for Pd/C from 52 to 75 min. These differences could be attributed to the dependence of step 6 and 8 on temperature where high temperature facilitates the removal of surface (i.e. adsorbed) oxygen.

References

- [1] M. Iwamoto, Future opportunities in Catalytic and Separation Technology, Studies in Surface science and Catalysis, Elsevier, Amsterdam-Oxford-New York-Tokyo, 1990.
- [2] K. C. Taylor, Catal. Rev.-Sci. Eng. 35 (1993) 457.
- [3] R.M. Heck, R.J. Farrauto, Catalytic Air Pollution Control, Commercial Technology, Van Nostrand Reinhold, 1995.
- [4] R. Krishnamurthy, S. S. C. Chuang, and M. W. Balakos, J. Catal. 157 (1995) 512.
- [5] B. J. Ku, J. K. Lee, D. Park, and H. Rhee, Ind. Eng. Chem. Res. 33 (1994) 2868.
- [6] M. Shelef, Catal. Rev.-Sci. Eng. 95 (1995) 209.
- [7] J.W. Hightower and D.A. Van Leirsburg, In The Catalytic Chemistry of Nitrogen Oxides; R.L. Klimisch, J.G. Larson, Eds.; Plenum Press, New York, p63 (1975).
- [8] Y. Li and W.K. Hall, J. Catal., 129 (1991) 202.
- [9] A. W. Aylor, S. C. Larsen J. A. Reimer and A. T. Bell, J. Catal. 157 (1995) 592.
- [10] S.S.C. Chuang and C-D. Tan, J. Phys. Chem. B, 101(1997) 3000.
- [11] Report on Basic Research Needs for Vehicles of the Future, P. M. Eisenberger (Editor), Princeton Materials Institute, Princeton University, 1995.
- [12] E. Suuberg, H. Teng and J. Calo, Energy and Fuels, 6 (1992) 398.
- [13] M.J. Illan-Gomez, A. Linares-Solano, L.R. Radovic and C. Salinas-Martinez de Lecea, Energy and Fuels, 10, 158, 1996.
- [14] E. Ruckenstein and Y.H. Hu, Ind. Eng. Chem. Res., 36 (1997) 2533.
- [15] T. Inui, T. Otowa, Y. Takegami, Ind. Eng. Chem. Prod. Res. Dev., 21 (1982) 56.
- [16] S.S.C Chuang, M.A. Brundage, M.W. Balakos and G. Srinivas Appl. Spectrosc. 49 (1995) 1151.
- [17] C.H. Rochester and B.J. Meldrum, J. Chem. Soc. Faraday Trans., 86 (1990) 3647.C.H.
- [18] M.A. Vannice, R.T.K. Baker and A. Dandekar, 'submitted' Carbon, 1998.
- [19] C. H. Rochester and B.J. Meldrum, J. Chem. Soc. Faraday Trans., 86 (1990) 1881.
- [20] R. Krishnamurthy, M.S. Thesis, The University of Akron, 1998.
- [21] R. Krishnamurthy and S. S. C. Chuang, J. Phys. Chem. 99 (1995) 16727.
- [22] K. Almusaiteer and S. S. C. Chuang, 'in press' J. Catal.
- [23] S.H. Oh and J.E. Carpenter, J. Catal. 101 (1986) 114.

- [24] R. D. Ramsier, Q. Gao, H.N. Walteburg, K.W. Lee, O.W. Nooij, L. Lefferts and J.T Yates Jr., *Surf. Sci.* 320 (1994) 209.
- [25] M.A. Salas-Peregrin, M. Primet and H. Praliaud, *Appl. Catal. B*, 8 (1996) 79.
- [26] A. T. Bell, *Metal-Surface Reaction Energetics: Theory and Applications to Hetrogeneous catalysis, Chemisorption, and Surface Diffusion*, E. Shustorovich (Editor), VCH, USA, 1991, Chap. 5, p191.
- [27] A. de Koster and R. A. van Santen, *J. Vac. Sci. Technol. A*, 6 (1988) 1128.

Table 1 Advantages and disadvantages of each approach

Approach	Disadvantages	Advantages
Catalytic reduction of NO with CO over three-way catalysts (Pt-Rh or Pd)	<ul style="list-style-type: none"> - Ineffective under net oxidizing conditions - Sulfur poisoning - High Pt and Rh metal costs 	<ul style="list-style-type: none"> - Simultaneous removal of CO, NO and hydrocarbons
Selective catalytic reduction with NH₃	<ul style="list-style-type: none"> - Special handling and storage of NH₃ - Special metering system to avoid NH₃ slippage - Very high capital costs 	<ul style="list-style-type: none"> - High NO removal efficiency in the presence of O₂.
Selective catalytic reduction with Hydrocarbons	<ul style="list-style-type: none"> - Further improvement in the selectivity to N₂ is needed. - Hydrocarbon slippage. 	<ul style="list-style-type: none"> - Potential for high NO removal efficiency in the presence of O₂
Direct decomposition of NO		<ul style="list-style-type: none"> - Chemical simplicity to form N₂ and O₂. - Eliminating the use of reducing agents
- Perovskite type catalysts	- Low activity and conversions	
- Cu-ZSM-5	- A narrow temperature window of operation and susceptible to water and SO ₂ poisoning	
- Pt/Al ₂ O ₃ based catalysts	- Low activity due to inability to desorb oxygen	
- Tb- promoted catalysts	- Loss of catalyst activity in the presence of O ₂ .	

Table 2 Activity and Selectivity of the catalysts for NO decomposition at 673 K

	Rh/Al ₂ O ₃	Rh/C	Pd/Al ₂ O ₃	Pd/C
Amount of Oxygen adsorbed (μmol/g) ^a	1303	1759	912	1800
Number of Metal Surface atom (μmol/g) ^b	880.4	937.1	686.5	636.8
W/F (g/cm ³ . s)	0.25	0.3	0.29	.03
Steady-state conversion after break through (%)	14.0	100 ^c	20.29	21.59
Yield of O ₂ (%) ^d	0.4	0.0	1.74	1.4
Yield of CO ₂ (%)	0.0	22.6	0.0	0.0

^a during stage 1 and 2 and normalized for g basis.

^b calculated from XRD data.

^c conversion during steady state formation of CO₂.

^d amount of O₂ produced/amount of NO in the reactant stream.

Table 3 **Proposed Mechanism for NO Decomposition**

	Reaction Steps	Rh/Al ₂ O ₃	Pd/Al ₂ O ₃	Rh/C	Pd/C
Step 1	$S^0 + NO \leftrightarrow S^0 - NO^-$	+	+	+	+
Step 2	$S^0 - NO^- + S^0 \rightarrow S-N + S-O (S^+)$	+	+	+	+
Step 3	$S-N + S-N \rightarrow 2S + N_2$	+	+	+	+
Step 4	$S^+ + NO \leftrightarrow S^+ - NO$	+	+	-	+
Step 5	$S-NO + S-N \rightarrow 2S + N_2O$	+	+	+	+
Step 6	$S-O + S-O \leftrightarrow 2S + O_2$	+	+	-	+
Step 7	$S-NO + S-O \rightarrow 2S + NO_2$	+	+	-	-
Step 8	$S-O + C \rightarrow S + C + CO_2$	-	-	+	-

Where S is Rh⁰ or Pd⁰ sites

+ indicates occurrence of the step

- indicates absence of the step

Figure 1a,b

Figure 2

Figure 3a,b

Figure 4

Figure 5a,b

Figure 6

Figure 7a,b

Figure 8