Report Title:

**ACTIVE CATHODES FOR SUPER-HIGH POWER DENSITY
SOLID OXIDE FUEL CELLS THROUGH SPACE CHARGE EFFECTS**

Type of Report: Quarterly Technical Report

Reporting Period Start Date: October 1, 2002
Reporting Period End Date: January 31, 2003
Principal Author: Professor Anil V. Virkar
Date Report Was Issued: April 14, 2003
DOE Award Number: DE-FC26-02NT41602

Name and Address of Submitting Organization:

Department of Materials Science & Engineering
122 S. Central Campus Drive
University of Utah
Salt Lake City, UT 84112

DISCLAIMER:

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United State Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

This report summarizes the work done during the first quarter of the project. Effort was directed in three areas: (1) The determination of the role of ionic conductor morphology, used in composite cathodes, on the ionic conductivity of the ionic conductor. It was shown that if the particles are not well sintered, the necks formed between particles will be very narrow, and the resulting conductivity will be too low (resistivity will be too high). Specifically, a mathematical equation was derived to demonstrate the singular nature of conductivity. (2) Nanosize powders of Sc-doped CeO_2 were prepared by combustion synthesis. The rationale is that the particle size of the composite electrode must be as small as possible to ensure a high ionic conductivity – and resulting in high performance in fuel cells. Di-gluconic acid (DGA) was used as fuel. The process led to the formation of nanosize Sc-doped CeO_2 . The powder was characterized by X-ray diffraction (XRD) and transmission electron microscopy (TEM). (3) Samples were sintered to form materials containing various levels of porosity, from ~3% to ~43%. Conductivity was measured over a range of temperatures by four probe DC method. It was observed that in highly porous samples, the conductivity was far lower than can be expected purely based on total porosity. The difference could be rationalized on the basis of the theoretical model developed.

TABLE OF CONTENTS

	Page
INTRODUCTION	5
EXECUTIVE SUMMARY	6
EXPERIMENTAL	8
RESULTS AND DISCUSSION	8
CONCLUSION	10
REFERENCES	18
LIST OF ACRONYMS AND ABBREVIATIONS	18

INTRODUCTION

It is now well known that electrode morphology has a profound effect on electrode polarization and thus on solid oxide fuel cell (SOFC) performance [1-4]. Recent work has shown that most of the polarization loss is associated with the cathode [5,6]. In addition to the morphological effect, it is also known that ionic conductivity of the cathode has a large effect on cathodic polarization. The grain size also has a large effect on conductivity [7]. It is desired that the cathode microstructure close to the electrolyte be as fine as possible. However, when the particle size is very fine, there can be a significant effect of space charge on transport [8-13]. It could either increase conductivity, or could decrease it. It is desired that the space charge be such that it enhances ionic conductivity of porous bodies. These two factors can substantially influence conductivity, and hence cathodic polarization. During the first quarter, efforts were devoted towards assessing the role of morphology on ionic conductivity of doped ceria.

EXECUTIVE SUMMARY

Solid oxide fuel cells (SOFC) can operate over a wide temperature range, from ~600 to 1000°C, and can use a variety of hydrocarbon fuels, once appropriately processed. The current target for SOFC is about 800°C, although efforts are presently underway to lower the operating temperature below 700°C. The largest voltage loss (polarization) in SOFC is known to occur in the cathode. There are two types of cathodic polarizations: (1) Concentration polarization – that associated with gas transport. (2) Activation polarization – that associated with the occurrence of the overall electrochemical reaction of charge transfer. The former is relatively small, as long as the cathode is thin and has sufficient porosity. The latter is the dominant one, and depends upon a number of microstructural and intrinsic – fundamental parameters. This research aims to address cathodic activation polarization. Specifically, this research aims to lower the cathodic polarization. Our prior work has shown that the effective cathodic polarization resistance depends upon the following factors. (1) The particle size of the ionic conductor in a composite cathode, comprising a two phase, porous, contiguous mixture of an ionic conductor and an electrocatalyst – which is an electronic conductor. In general, the smaller the particle size of the ionic conductor, the lower is the cathodic activation polarization. (2) The ionic conductivity of the ionic conductor also has a significant effect – the higher the ionic conductivity, the lower is the cathodic polarization. (3) Intrinsic charge transfer resistance – the lower the intrinsic charge transfer resistance, the lower is the cathodic activation polarization.

The above factors themselves depend upon some other fundamental parameters. It is known that in the majority of the ionic conductors, the smaller the grain size, the higher is the net resistivity. This is attributed to grain boundaries, which usually offer resistance to ion transport. Part of this resistance is attributable to space charge effects, which tend to lower oxygen vacancy concentration near grain boundaries. Depending upon the dopant type and amount, it is in principle possible to actually enhance the oxygen vacancy concentration near grain boundaries. If this can be achieved, significant lowering of cathodic polarization can occur. This research aims to identify fundamental parameters, which tend to increase oxygen concentration near grain boundaries. This is expected to depend upon the chemistry of the material as well as processing.

The other factor involves the nature of inter-particle necks. If the contact between particles is poor (small), the overall resistance can be large, leading to high cathodic polarization. During the current reporting period, the effect of inter-particle neck size on total conductivity of porous bodies was theoretically analyzed. On the experimental side of the work, nanosize powders of Sc-doped CeO₂ were synthesized using the combustion method. It was observed that the ratio of fuel to precursor affects the maximum temperature achieved, and also the size of the powder formed. The powders were analyzed using X-ray diffraction and transmission electron microscopy. X-ray studies showed that the particle size is in the nanometer range. Transmission electron microscopy showed that the particles were well crystallized, and lattice image fringes could be observed. Samples were sintered to varying degrees of porosities – ranging between ~3% and ~43%, and their conductivity was measured over a range of temperatures. It was noted that the conductivity of the samples with the highest porosity was much lower than can be expected based on the volume fraction

porosity present. The difference was rationalized on the basis of the theoretical model developed.

EXPERIMENTAL

During this reporting period, efforts were directed in the following areas.

- (1) Theoretical analysis of the effect of neck size in contacting spheres on the conductivity of porous bodies. The approach was analytical, with focus on obtaining an analytical equation in a parametric form.
- (2) Synthesis of nanosize powders of Sc-doped CeO₂. The following procedure was used. Sc(NO₃)₃ and Ce(NO₃)₃ were mixed in requisite proportions to form a single phase Sc-doped CeO₂ of the CaF₂ structure with Sc content equal to 20% and Ce content equal to 80%, and dissolved in de-ionized water. Then di-gluconic acid (DGA) was added in requisite amount, which varied between 35% and 100% on a molar basis. The solution was heated in a stainless steel beaker on a hot plate. Once all of the water was vaporized, the mixture combusted, resulting in rapid rise in temperature. The temperature was recorded by a thermocouple. The measured temperature was, however, much lower than the adiabatic flame temperature. The resulting product was a very fine powder.
- (3) The powder was subsequently characterized by X-ray diffraction (XRD) and transmission electron microscopy (TEM). XRD peak widths were used to estimate the crystallite size. TEM micrographs were used to assess the crystallinity of the powder, and to determine the degree of agglomeration.
- (4) Powder compacts were formed by die-pressing. The compacts were then sintered in air over a range of temperatures. The objective was to make samples of varying porosity levels.
- (5) Total conductivity of the samples of varying porosity levels was measured as a function of temperature using a four-probe DC method.

RESULTS AND DISCUSSION

Effect of Inter-particle Contact on Conductivity: One important factor, which dictates cathodic polarization is the degree to which the cathode has sintered. The objective is to ensure that the cathode contains sufficient amount of porosity, and at the same time, inter-particle contact area is as large as possible. During the past three months, both theoretical and experimental work has been conducted. On the theoretical side, the problem considered is that of conductivity of partially sintered body made of spheres (Figures 1(a) and 1(b)). Simple, one-dimensional analysis shows that for spheres of radius R , and contact radius of r_o , the resistance of the truncated sphere is given by

$$\Omega \approx \frac{\rho}{2\pi R} \ln \left\{ \frac{1 + \sqrt{1 - \alpha^2}}{1 - \sqrt{1 - \alpha^2}} \right\} = \frac{1}{2\pi\sigma R} \ln \left\{ \frac{1 + \sqrt{1 - \alpha^2}}{1 - \sqrt{1 - \alpha^2}} \right\} \quad (1)$$

where ρ (σ) is the resistivity (conductivity) of the material and the parameter α is given by

$\alpha = \frac{r_o}{R}$. The approximate resistivity of the porous body also scales proportionately. The

logarithmic factor with $1 - \sqrt{1 - \alpha^2}$ in the denominator shows that as the contact radius approaches zero that is as $\alpha \rightarrow 0$, the resistance becomes infinitely large. Table I gives the estimated value of R for various values of α .

Table I

α	R
0	∞
0.1	$5.986 \rho / 2\pi R$
0.2	$4.585 \rho / 2\pi R$
0.3	$3.748 \rho / 2\pi R$
0.4	$3.134 \rho / 2\pi R$
0.5	$2.634 \rho / 2\pi R$
0.7071	$1.763 \rho / 2\pi R$

Table I shows the importance having the contact radius, r_o , as large as possible. Alternatively, the conductance may be given by

$$G \approx \frac{2\pi R}{\rho} \ln \left\{ \frac{1 - \sqrt{1 - \alpha^2}}{1 + \sqrt{1 - \alpha^2}} \right\} = 2\pi R \sigma \ln \left\{ \frac{1 - \sqrt{1 - \alpha^2}}{1 + \sqrt{1 - \alpha^2}} \right\} \quad (2)$$

Measurement of conductivity as a function of temperature in samples of varying porosity levels: Experimental work has been conducted on Sc-doped CeO₂. The approach was to synthesize nanosize Sc-doped CeO₂ by combustion synthesis. Figure 2 shows XRD traces of as-synthesized powders. Figure 3 shows a transmission electron micrograph (TEM) of a sample of nanosize Sc-doped CeO₂ formed by combustion synthesis. The powder was subsequently consolidated and sintered at various temperatures to form samples with various porosity levels. Figures 4(a) and 4(b) are scanning electron micrographs of sintered samples. The corresponding porosities are ~3.3% and ~24%, respectively. Samples with as high as ~43% porosity were also made. However, it was difficult to polish them. Table II shows the measured conductivity as a function of temperature for the three samples. Note that the conductivity of highly porous samples is much lower than can be rationalized on the basis of phenomenological equation, namely

$$\sigma_{porous} \approx \sigma(1 - V_v) \quad (3)$$

where V_v is the volume fraction of porosity. Very low conductivity of the highly porous samples, however, can be rationalized on the basis of proposed model. The second column in Table II gives conductivity after annealing at 1200°C for 4 hours. The decrease in conductivity is likely related to space charge effects. Significance of these studies will be discussed in subsequent reports, as more data become available.

Work is underway on modeling of the space charge effects, and will be included in future reports.

Table II: Sintering conditions, porosity and conductivity as a function of temperature.
Sintered at 1450 °C/4 hours

Temperature (°C)	Conductivity (S/cm)	
	ScDC 80/20(3.3% porosity)	ScDC 80/20(3.3% porosity) Annealed at 1200 °C/ 4 hours
650	0.029	0.00653
700	0.0451	0.01561
750	0.066	0.03033
800	0.0906	0.05115

Sintered at 1300 °C/2 hours

Temperature (°C)	Conductivity (S/cm)	
	ScDC 80/20(24.3% porosity)	ScDC 80/20(24.3% porosity) Annealed at 1200 °C/ 4 hours
650	0.01228	0.0024
700	0.02005	0.00585
750	0.02951	0.01524
800	0.04104	0.03012

Sintered at 1200 °C/4 hours

Temperature (°C)	Conductivity (S/cm)	
	ScDC 80/20(43.3% porosity)	ScDC 80/20(43.3% porosity) Annealed at 1200 °C/ 4 hours
650	5.52×10^{-5}	7.05×10^{-6}
700	1.45×10^{-4}	3.1×10^{-5}
750	2.96×10^{-4}	1.1×10^{-4}
800	5.533×10^{-4}	3.4×10^{-4}

CONCLUSION

Equation (1) is a parametric form of the resistance of a compact of spherical particles, and equation (2) is a parametric form of the conductance. When the contact radius is zero, the resistance becomes infinite – singular. What this shows is that if the sintering poor, the ionic resistance will be very large, and will have an adverse effect on SOFC performance. Indeed, Table II shows that conductivity of samples with ~43% porosity is less than 1% of the value of the sample with ~3% porosity. This difference cannot be rationalized on the basis of total porosity. Also, it is to be noted that when a composite cathode is made, by mixing doped CeO₂ with an electrocatalyst such as Sr-doped LaMnO₃ (LSM), the measured total conductivity of the cathode may well be high, which is due to the electronic conductivity of LSM. However, the cathode performance may be very poor. The only way the expected performance of a composite cathode can be judged is by measuring the ionic conductivity of

porous ceria, or whatever is the ionic conductor. The present work has also demonstrated the use of combustion synthesis for the fabrication of composite cathodes.

Figure 1(a): A schematic of a partially sintered material with particle size R and contact radius of r_0 . This schematic shows a structure with a relatively small contact radius. Thus, we expect the effective resistivity to be relatively high.

Figure 1(b): A schematic of a partially sintered material with particle size R and contact radius of r_0 . This schematic shows a structure with a relatively large contact radius. Thus, we expect the effective resistivity to be relatively low.

CeO_2 (Scandia-doped)

Figure 2: XRD patterns of Sc-doped CeO_2 formed by combustion synthesis. Note the large peak width, indicative of nanosize of the powder formed.

Figure 3: A transmission electron micrograph (TEM) of nanosize Sc-doped CeO₂ (Sc:Ce = 20:80) showing that the individual crystallite size is ~3 to 5 nm.

Magnification 3500

Figure 4(a): Sc₂O₃-doped ceria [Sc:Ce=20:80 (molar ratio)] Dense Bar (Porosity = 3.8%). Sintering at 1450 °C/4hours. Thermal etching at 1300 °C/3hours. Note relatively coarse grain size. Conductivity data are given in Table II.

Magnification 3500

Figure 4(b): Sc₂O₃-doped ceria [Sc:Ce=20:80 (molar ratio)]Porous Bar (Porosity = 23.8%). Sintering at 1300 °C/2 hours. Thermal etching at 1300 °C/3hours. Note relatively fine grain size. Conductivity data are given in Table II.

REFERENCES

- 1) T. Kenjo, S. Osawa, and K. Fujikawa, *J. Electrochem. Soc.*, **138** 349 (1991).
- 2) C. W. Tanner, K-Z. Fung, and A. V. Virkar, *J. Electrochem. Soc.*, **144** 21-30 (1997).
- 3) H. Deng, M. Zhou, and B. Abeles, *Solid State Ionics*, **74** 75 (1994).
- 4) I. V. Murygin, *Elektrokhimiya*, **23** [6] 740 (1987).
- 5) A. V. Virkar, J. Chen, C. W. Tanner, and J-W. Kim, *Solid State Ionics*, **131** 189 (2000).
- 6) F. Zhao, Y. Jiang, G-Y. Lin, and A. V. Virkar, pp. 501 in SOFC VII, edited by H. Yokokawa and S. C. Singhal, Electrochemical Society Publication, Pennington, NJ, (2001).
- 7) M. J. Verkerk, B. J. Middlehuis, and A. J. Burggraaf, *Solid State Ionics*, **6** 159 (1982).
- 8) X. Guo, *Solid State Ionics*, **81** 235-242 (1995).
- 9) X. Guo, *Solid State Ionics*, **99** 137-142 (1997).
- 10) J. Frenkel, p. 37 in 'Kinetic Theory of Liquids', Dover, NY (1946).
- 11) K. Lohvevec, *J. Chem. Phys.*, **21** [7] 1123-1128 (1953).
- 12) K. L. Kliewer and J. S. Koehler, *Phys. Rev.*, **140** [4A], A1226-A1240 (1965).
- 13) K. L. Kliewer, *Phys. Rev.*, **140** [4A], A1241-A1246 (1965).

LIST OF ACRONYMS AND ABBREVIATIONS

DC:	Direct current
DGA:	Di-gluconic acid
LSM:	Sr-doped LaMnO ₃
SOFC:	Solid oxide fuel cell
TEM:	Transmission electron microscopy
XRD:	X-ray diffraction