Report Documentation Page Information

Title and Subtitle: AISI/DOE Technology Roadmap Program -
Effects of Residuals in Carbon Steels

Authors: George E. Ruddle

Performing Organization Names, Addresses:

Materials Technology Laboratories (MTL)
Canada Centre for Mineral and Energy Technology (CANMET)
Natural Resources Canada
568 Booth Street
Ottawa, Ontario K1A 0G1
Canada

Abstract:

An experimental study of the effects of residual elements in carbon steels was carried out to gain better understanding and control of the effects of residual elements emanating from recycled steel scrap. Two plain carbon steel grade compositions (one medium-carbon and one low-carbon), residual elements and levels, and four areas of study, were selected on the bases of a comprehensive literature survey and consultation with sponsor steel companies. The influence of residuals (Cu, Sn, Ni, P, Si, up to the levels studied here), on these laboratory produced hot rolled steels was studied in the areas of a) hot ductility, b) surface hot shortness, c) scale formation and adherence, and d) embrittlement and mechanical properties. This report summarizes the experimental procedures, results, discussion and conclusions of this study. The relevance of the study is also discussed in relation to steel processing and product properties and in relation to energy consumption and environmental compliance.

Some of the major findings are:

- Addition of Cu and Sn decreased hot ductility in all steels, while addition of Ni to the Cu-, Sn-containing steels improved hot ductility in medium carbon steels only
- Ductility trough minima occurred at 700 - 800° C in the medium carbon steels and 800 - 900° C in the low carbon steels.
- Cu additions, in the absence of Ni and Sn, in low carbon steels did not result in development of deep surface cracks, while Cu additions in excess of Ni in medium carbon steels did result in deep surface cracks at lower temperatures.
- Additions of Cu, Sn, Ni and P had little or no effect on oxide growth rates. However, oxidation rates increased when moisture was introduced to the oxidation furnace atmosphere.
- Scale adherence increased with increasing oxidation temperature, increased dramatically with addition of moisture to the oxidation atmosphere, and increased when residual Cu and Ni were present in the medium carbon steels, particularly at higher temperatures in moist atmosphere.
- Scale adherence did not consistently increase in these steels with increasing Si content up to 0.3%.
- Increasing residual content increased tensile properties (YS and UTS), primarily by ferrite grain refinement, and secondarily by solid solution hardening.
- Addition of residuals had little effect on Charpy impact toughness.

Sponsor TBD Report No.: _____

AISI/DOE Technology Roadmap Program

Final Report

Effects of Residuals in Carbon Steels

by

George E. Ruddle

November 25, 2002

Work Performed under Cooperative Agreement

No. DE-FC07-97ID13554

Prepared for

U.S. Department of Energy

Prepared by

**American Iron and Steel Institute
Technology Roadmap Program Office
Pittsburgh, PA 15220**

DISCLAIMER

“Any opinions, findings, and conclusions or recommendations expressed in this material are those of the author(s) and do not necessarily reflect the views of the US Department of Energy.”

Number of pages in this report: 58

For availability of this report contact:
Office of Scientific and Technical Information,
P. O. Box 62, Oak Ridge, TN 37831. (615) 576-8401.

TABLE OF CONTENTS

	Page
TABLE OF CONTENTS	iii
LIST OF FIGURES	v
EXECUTIVE SUMMARY	viii
ACKNOWLEDGEMENT	xii
1. INTRODUCTION	1
2. EXPERIMENTAL	2
3.2 SURFACE HOT SHORTNESS	7
3.2.1 Medium-Carbon Steels	7
3.2.2 Low-Carbon Steels	7
3.3 SCALE FORMATION AND ADHERENCE	8
3.3.1 Scale Growth	8
3.3.1.1 Medium-carbon steels	8
3.3.1.2 Low-carbon steels	8
3.3.2 Scale Adherence	9
3.3.2.1 Medium-carbon steels	9
3.3.2.2 Low-carbon steels	9
3.4 MECHANICAL PROPERTIES	9
3.4.1 Medium- and Low-Carbon Steels	9
4.0 DISCUSSION	10
4.1 HOT DUCTILITY	10
4.2 SURFACE HOT SHORTNESS	11
4.3 SCALE FORMATION AND ADHERENCE	13
4.3.1 Scale Growth	13
4.3.2 Scale Adherence	14

4.4	MECHANICAL PROPERTIES	14
4.5	RELEVANCE TO THE STEEL INDUSTRY	15
4.5.1	Hot Ductility	15
4.5.2	Surface Hot Shortness	16
4.5.3	Scale Formation and Adherence	17
4.5.4	Mechanical Properties	17
4.6	RELEVANCE TO ENERGY/ENVIRONMENT	18
5.0	CONCLUSIONS	19
5.1	HOT DUCTILITY	19
5.1.1	Medium-Carbon Steels	19
5.1.2	Low-Carbon Steels	19
5.2	SURFACE HOT SHORTNESS	20
5.2.1	Medium-Carbon Steels	20
5.2.2	Low-Carbon Steels	20
5.3	SCALE FORMATION AND ADHERENCE	21
5.3.1	Scale Growth	21
5.3.2	Scale Adherence	21
5.4	MECHANICAL PROPERTIES	22
	REFERENCES	23

LIST OF FIGURES

Fig. 1.	Effect of deformation temperature on hot ductility (RA%) and maximum Load of the base medium carbon steel, M1	24
Fig. 2.	Fractured Gleeble samples of Steel M1	24
Fig. 3.	Hot ductility curve and fracture surfaces of M1 after Gleeble testing at different temperatures	25
Fig. 4.	Fracture surface of M1 and EDX analysis of Mn sulphide particle (at arrow) After Gleeble testing at 700°C	26
Fig. 5.	Effect of deformation temperature on hot ductility (RA%) and maximum Load of the base low carbon steel, L1	27
Fig. 6.	Fractured Gleeble samples of Steel L1	27
Fig. 7.	Fracture surfaces of L1 after Gleeble testing at different temperatures	28
Fig. 8.	Fracture surfaces of L1 after Gleeble testing at different temperatures	29
Fig. 9.	L2 WQ (600°C), showing proeutectoid grain-boundary ferrite	30
Fig. 10.	Average surface crack depth of M-Series alloys after tensile to 40% elongation with a strain rate of 5 s ⁻¹ at 1100°C	30
Fig. 11.	Depth distribution of surface cracks of M-Series alloys after tensile testing To 40% elongation with a strain rate of 5 s ⁻¹ at 1100°C	31
Fig. 12.	SEM photograph showing scale/metal interface properties of M6 alloy Subjected to tensile testing with a strain rate of 5 s ⁻¹ at 1100°C	32
Fig. 13.	Average surface crack depth of L-Series alloys after tensile testing to 40% elongation with a strain rate of 5 s ⁻¹ at 1100°C	33
Fig. 14.	Depth distribution of surface cracks of L-Series alloys after tensile Testing to 40% elongation with a strain rate of 5 s ⁻¹ at 1100°C	33
Fig. 15.	Weight change curves for the oxidation of medium carbon steel alloys	

At 1200°C in dry air atmosphere	34
Fig. 16. Effect of furnace atmosphere on the total weight change after one hour of Oxidation of medium carbon steel alloys at 1200°C	34
Fig. 17. Effect of temperature on the total weight change from oxidation of medium Carbon steel alloys for one hour in air-H ₂ O atmosphere	35
Fig. 18. SEM images of oxides formed on medium carbon steel M7 and M9 after one hour of oxidation at 1200°C in dry air	35
Fig. 19. SEM images of oxides formed on medium carbon steel M9 after one hour of oxidation at 1100°C in air-H ₂ O atmosphere	36
Fig. 20. Effect of furnace atmosphere on the total weight change after one hour of oxidation of low carbon steel alloys at 1200°C	36
Fig. 21. Effect of temperature on the total weight change after one hour of oxidation of low carbon steel alloys in air-H ₂ O atmosphere	37
Fig. 22. Effect of furnace atmosphere on the scale adherence of medium carbon Alloys oxidized for one hour at 1200°C	37
Fig. 23. Effect of oxidation temperature on the scale adherence of medium carbon Alloys oxidized for one hour in moist air atmosphere	38
Fig. 24. Effect of oxidation temperature on the scale adherence of low carbon steel Alloys oxidized for one hour in moist air	38
Fig. 25. Effect of furnace atmosphere on the scale adherence of low carbon alloys oxidized for one hour at 1200°C	39
Fig. 26. Engineering tensile stress vs strain curve of hot-rolled L1 and L12 steel samples	39
Fig. 27. Effect of residuals on strengths of med.-C steels in hot-rolled condition	40
Fig. 28. Effect of step-cooling treatment on yield strengths of medium carbon steels	40
Fig. 29. Charpy transition curves of med.-C steels in the hot-rolled condition	41

Fig. 30.	Charpy transition curves of low-C steels in hot-rolled condition	41
Fig. 31.	Effect of residuals on Charpy transition curve of M3 steel (HR – hot-rolled; SC – step-cooled)	42
Fig. 32.	Effect of residuals on Charpy transition curve of L3 steel (HR – hot-rolled; SC – step-cooled)	42
Fig. 33.	SEM fractographs of L13 Charpy specimens tested at -196°C	43
Fig. 34.	SEM photograph of AES L14 (SC) sample A showing spots for Auger Analysis, enlarged view (orig. 635x, 200 μm edge-to-edge)	44
Fig. 35.	Typical Auger spectra of L13 (SC) – Sample A, Spot 2 showing an AES Spectrum at a segregated grain boundary facet	44
Fig. 36.	Schematic diagram of ductility curve defining the trough area and Temperature of R1=60% reduction in area	45
Fig. 37.	Comparison of ductility curves of the base low- and medium-carbon steels, i.e., L1 and M steels	

EXECUTIVE SUMMARY

An experimental study of the effects of residual elements in carbon steels was carried out under the Technology Roadmap Program Agreement between the American Iron and Steel Institute (AISI) and United States Department of Energy (DOE) to gain better understanding and control of the effects of residual elements emanating from recycled scrap steel. Information provided from this study is intended to help steel companies to increase the use of recycled scrap steel in the production of modern steel grades with potential benefits of reductions in production cost, energy consumption and CO₂ gas emission. Steel production from scrap charge has been reported to require 74% less energy than production from virgin ore material and results in 67% less environmentally harmful CO₂ gas emission. Increase of scrap-based steel production potentially can derive these benefits without loss in productivity.

On the basis of a comprehensive literature survey conducted in the initial phase of this project and consultation with the sponsor steel companies, the compositions of two steel grades (one medium-carbon and one low-carbon) with residual elements and levels of interest were selected, and the experimental plan was agreed upon for study in four areas where residuals can have effect: 1. hot ductility, 2. surface hot shortness, 3. scale formation and adherence, and 4. embrittlement and mechanical properties.

Twenty-three steel alloys (10 medium-carbon and 13 low-carbon) were cast in 23 four-ingot heats using vacuum-furnace melting. The medium-carbon (0.20 wt % C) series included the base composition and combinations of Si, Cu, Sn and Ni in relation to EAF steelmaking practice. The low-carbon (0.04 wt % C) series included the base composition and combinations of Si, Cu, Sn, Ni and P related to integrated-mill hot-strip production, and one composition with higher Mn typical of plate production. Residual (Cu, Ni, Sn) levels were higher in the medium-carbon steels than in the low-carbon steels. Cast ingots were reheated and hot-rolled to plate/sheet thickness from which test samples were machined as required for the parts of the experimental study.

In the study of hot ductility, Gleeble test samples were heated to melting temperature, control-cooled to test temperature, then deformed in tension to fracture. Hot ductility curves (% reduction of area vs. test temperature) were generated from test temperatures ranging 1100 to 600°C. The study of surface hot shortness entailed hot-tensile testing of samples in-situ in a furnace. Samples were heated and held one hour at test temperature to allow formation of surface oxide scale, then deformed in tension to 40% elongation; test temperatures ranged from 1000 to 1300°C. Sample gauge length sections were examined for extent of surface crack formation. In scale growth tests conducted by thermogravimetric analysis, samples were reacted for one hour at temperatures of 1000, 1100 and 1200°C in dry and moist atmospheres. In scale adherence tests, samples were reacted in the same oxidation conditions, then immediately removed from the oxidation furnace to a bend test from which the amount of adherent scale was determined. Tensile and Charpy-impact mechanical properties were tested on samples from as-hot-rolled plate material, and from plate material subjected to a step-cooling heat-treatment to maximize segregation effects. In all cases, optical/electron microscopic analysis methods were applied as required to characterize microstructural features in the tested samples.

The study of residual effects on hot ductility showed the following:

- Addition of Cu and Sn at the levels of this study decreased hot ductility; addition of Ni at the levels of this study to the Cu- and Sn-containing medium-carbon steels improved ductility, but not in the low-carbon steels where the residual (Ni, Cu, Sn) levels were lower.
- Ductility trough minima occurred at 800-700°C in the medium-carbon steels and at 900-800°C in the low-carbon steels.
- All steels exhibited fully ductile transgranular failure at high temperatures (>1000°C) and embrittled intergranular failure at the minimum ductility temperatures.
- Fine (Mn) and (Mn, Fe) sulphide particles along grain boundaries were responsible for ductility loss and intergranular failure; Cu and Sn segregation observed at the MnS particles in the medium-carbon steels would enhance this embrittlement failure. No enrichment or segregation of Cu or Sn was observed in relation to fracture in limited examination of the low-carbon steels.
- A new factor, Relative Trough Area (RTA), was defined as a useful tool for comparing ductility curves. Steels in both the medium- and low-carbon series were ranked for ductility in terms of their RTA values. Also, on the basis of 60% critical reduction of area, critical temperatures in the low-ductility region of the steels were measured with relation to prevention of transverse cracking in a continuous-casting process.

The study of residual effects on surface hot shortness showed the following:

- Cu addition at the level studied, in the absence of Ni and Sn, in the low-carbon steels did not result in development of deep surface cracks; Cu addition in excess of Ni content at the residual levels studied in the medium-carbon steels did result in deep surface crack formation at the lower temperatures, but not at the higher temperatures. (Residual levels were higher in the medium-carbon steels than in the low-carbon steels.)
- Addition of Ni to the low-carbon steel containing Cu and intermediate level of Sn did not suppress development of deep surface cracks at the lower temperatures. In the medium-carbon steels where the residual (Ni, Cu, Sn) levels were higher, addition of Ni in equal amount to Cu content did suppress deep crack formation when intermediate level of Sn was present, but not when high level of Sn was present.
- Surface crack depth decreased dramatically at the higher temperatures in the medium- and low-carbon steels.
- In general, the results provided guideline data on acceptable residual levels and reheat temperatures that would not result in deep surface crack formation during reheating and hot-rolling of the selected grades

of steel.

The results of scale growth tests on medium- and low-carbon steels showed the following:

- Additions of residual elements Cu, Sn, Ni and P, at the levels of this study, had little or no effect on oxide growth rates after one hour of oxidation. Oxidation rate increased with increasing temperature, and also when moisture was introduced to the oxidation furnace atmosphere.
- The oxide scale consisted of an inner wustite layer (FeO), an intermediate magnetite layer (Fe₃O₄), and in some cases a thin outer layer of hematite (Fe₂O₃).
- Residual element additions resulted in additional phases such as metallic compounds and iron silicates embedded in the inner wustite layer at and near the steel/scale interface.

The results of scale adherence tests showed the following:

- Scale adherence increased with increasing oxidation temperature; increased dramatically with addition of moisture to the oxidation atmosphere, particularly at the higher temperatures; and increased when residual Cu and Ni were present, particularly at the higher temperatures in moist atmosphere. These effects occurred in the medium-carbon steels; scale adherence in the low-carbon steels where the residual levels were lower was minimal in comparison.
- Scale adherence did not consistently increase in steels containing the higher level of Si (0.3%).
- The results provided guideline data on steel composition and oxidation temperature and atmosphere conditions required to minimize scale adherence resulting from a steel reheating process.

The study of residual effects on mechanical properties of medium- and low-carbon steels showed the following:

- Addition of residuals decreased average ferrite grain size by up to 29%.
- Increasing residual content increased tensile properties (YS and UTS), primarily by ferrite grain refinement and secondarily by solid-solution hardening.
- Addition of residuals in the hot-rolled steels had little effect on Charpy impact toughness; however, the higher Mn and Si in the plate-composition steel significantly increased impact toughness by lowering the 40 J transition temperature by 80°C. After step-cooling heat-treatment to maximize segregation, transition temperatures were increased by up to 28°C in the steels with the higher Mn and Si contents and were changed very little in the steels with low Mn and Si levels. This indicated that grain boundary segregation requires the presence of alloy elements such as Mn and Si.
- Sn enrichment (segregation) was found on intergranular facets in the embrittlement-sensitive steels after the step-cooling heat-treatment.
- The results indicated how the microstructure developed in reheating and hot-rolling processing of the steel

can affect its mechanical properties. Embrittlement effects of residual segregation in the as-hot-rolled steels were small.

In relation to energy and environment, the results of this experimental study provided information on effects of selected residual compositions and processing parameters on properties of selected medium-carbon and low-carbon steel grades which steel companies can apply to design of steel furnace-charges, processes and products, utilizing recycled scrap steel with the ensuing benefits of reduced energy consumption, reduced cost and environmental compliance.

ACKNOWLEDGEMENTS

The author acknowledges the research and documentation work of the following colleagues at the Materials Technology Laboratory (CANMET) who actually carried out the experimental program: D. Emadi, O. Dremailova, E. Essadiqi, H.T. Abuluwefa, I. Al-Taie, V. Kao, C. DeRushie, S. Xu, J.R. Brown and W.R. Tyson. The supporting work of CANMET staff, and of Aerospace Research Institute (NRC) staff (for surface-hot-shortness tensile testing), are also gratefully acknowledged. Dr. E. Essadiqi, Program Manager, Efficient Metal Production, is acknowledged for helpful scientific and administrative leadership and support throughout this project.

The work summarized in this report was the experimental study phase of a contract in the American Iron and Steel Institute (AISI) Technology Roadmap Program sponsored by Office of Scientific and Technical Information, Department of Energy (DOE), United States Government, and by the following participating steel companies:

AK Steel
IPSCO, Inc.
LTV Steel Company, Inc.
National Steel
The Timken Company
U.S. Steel Research
Weirton Steel Corp.

1. INTRODUCTION

Amongst the traditional materials in wide use today, steel has the highest recycling rate [1]; more than twice as much steel is being recycled as all other metallic materials combined [2]. Use of recycled scrap steel in electric arc furnace steelmaking, and to a lesser extent in integrated plant steelmaking, has been increasing as a result of economic forces to improve processing and production efficiency and legislative forces related to sustainable development and environmental concerns. As levels of residual impurity elements entering the steelmaking process from scrap feed are increasing with increased scrap use and repeated recycling, the ability to control the detrimental effects of residuals, and the need to define tolerable residual levels relative to product quality and performance in modern steel grades, are of major concern.

The American Iron and Steel Institute (AISI) under its Technology Roadmap Program Agreement with United States Department of Energy (DOE) has contracted Materials Technology Laboratory, CANMET, Natural Resources Canada, Ottawa, to conduct a research study on “Effects of Residuals in Carbon Steels”. The research study project consisted of two phases with the following objectives.

Phase I: State-of-knowledge survey: Objective: Identify the state-of-knowledge of the effects of residual elements on surface quality during casting and rolling processes and on the final product properties of carbon steels. The survey included the following six topic areas:

- hot shortness and ductility during casting and rolling
- scale formation and adherence
- embrittlement and mechanical properties
- weldability
- corrosion properties
- galvanizing properties.

Phase II: Experimental study: Objective: Evaluate and characterize the effects of residuals on a range of properties in two selected grades of steel, one low-carbon and one medium-carbon, in the following three selected topic areas:

- hot shortness and ductility during casting and rolling
- scale formation and adherence
- embrittlement and mechanical properties.

On the basis of the Phase I survey report and in consultation with the participating steel companies, steel chemistries and specific residual elements and levels of interest, and an experimental work plan, were proposed for the two selected grades of steel for the Phase II study. The Phase II proposal was approved, and experimental work was completed at CANMET. This report summarizes the detailed experimental work and the results thereof.

2. EXPERIMENTAL

2.1 MATERIAL

Twenty-three steel alloys [10 medium-carbon (designated M1-M10) and 13 low-carbon (designated L1-L13) steels] were cast in 23 four-ingot heats. The medium-carbon (0.20 wt % C) steel alloys contained, in addition to the base composition levels, combinations of one level of Si, two levels of Cu, two levels of Sn and two levels of Ni, primarily in relation to EAF steelmaking practice. The low-carbon (0.04 wt % C) steel alloys contained, in addition to the base composition levels, combinations of one level of Si, one level of Cu, two levels of Sn, one level of Ni and one level of P, in relation to integrated-mill hot-strip production. Twelve of the thirteen low-carbon steels contained Mn at the level typical of hot-strip production, and the remaining steel contained a higher level of Mn typical of plate production. The residual levels were substantially higher in the medium-carbon steels than in the low-carbon steels. The steel heats each entailed vacuum-furnace melting of a 500 lb (200 kg) charge, using Al-killing practice, and casting into permanent cast-iron molds to produce four 5 x 6 x 14 in. (12.5 x 15 x 35 cm) ingots. The cast ingots were cropped to 8-10 in. (20-25 cm) length to eliminate casting shrinkage defects.

The cast ingots were reheated in an air-atmosphere furnace for 3 h at 1100°C and 1120°C for the medium-carbon and low-carbon steels, respectively. Reheated ingots were hot-rolled to 0.6 in. (16 mm) thick plate in a pilot-scale reversing mill, using a controlled 14-pass temperature/thickness reduction schedule with temperature monitored by a thermocouple embedded in the midpoint of the side of the ingot. Rolling finish-temperatures were 860°C and 950°C for the medium-carbon and low-carbon steels, respectively, above the respective A_{r3} transformation temperatures. Bar sections cut from the steel plates were further reheated and hot-rolled to 7.5 mm thick sheet as required for the scale formation and adherence study.

Test samples were cut and machined from the hot-rolled plates as required and described below for the four parts of the experimental study.

2.2 HOT DUCTILITY

The hot ductility study examined six medium-carbon (0.20 wt % C) steel compositions including the base composition levels and combinations of two residual levels of Cu, of Sn and of Ni; and seven low-carbon (0.04 wt % C) steel compositions including the base composition levels and combinations of high residual Cu, medium residual Sn, high residual Ni and high P. The residual levels in the medium-carbon steels were higher than in the low-carbon steels.

Based on preliminary Gleeble test work indicating greater ductility-loss sensitivity in longitudinal-oriented samples (parallel to plate rolling direction), Gleeble test samples, 9.84 mm dia x 125 mm long, were machined from the hot-rolled steel plates with axis parallel to the rolling direction.

Gleeble test samples surrounded by a quartz glass sleeve were heated to melting temperature in argon atmosphere, then cooled through solidification at 15°C/s to the test temperature, held for 30 s and then

pulled in tension at the test temperature at 0.005/s strain rate until fracture. At least 2-4 samples of each steel were tested at temperatures of 1100, 1000, 900, 850, 800, 750, 700 and 600°C to generate average data for hot ductility curves. Also, samples were quenched from the test temperatures, without tensile deformation, in order to examine ferrite phase formation along grain boundaries. A few selected samples were quenched after tensile deformation to maximum load, without fracture, for Auger microscopy studies. From these quenched samples, small rod samples, 3 mm dia x 20 mm long, with a circular 1 mm deep V-notch at 9 mm from one end, were machined for Auger in-situ fracture test and examination.

Gleeble tensile-tested samples were measured for percentage reduction of area at fracture, and average data were plotted in reduction-of-area (RA) versus temperature curves to evaluate hot ductility. The fracture surfaces and the microstructure near the fracture surfaces of selected test samples were examined by optical microscopy, scanning electron microscopy (SEM), electron microprobe analysis (EMPA) and Auger electron spectroscopy (AES).

2.3 SURFACE HOT SHORTNESS

The study of surface hot shortness was conducted on the same six medium-carbon (0.20 wt % C) and seven low-carbon (0.04 wt % C) steel compositions as described above for the hot ductility study.

Tensile test samples, 12.5 mm dia x 150 mm long with 6.3 mm gauge dia x 19 mm gauge length, were machined from the hot-rolled plates transverse to the rolling direction. In order to maintain mechanical and thermal stability in the test sample, hot-tensile tests were performed in a vertical uniaxial digital-servocontrolled electrohydraulic 100 kN testing system with in-situ dual-zone furnace. The test entailed mounting of the sample in zero-load position, heating the gauge length of the sample in air atmosphere at a pre-set rate to the test temperature, holding at the test temperature for one hour to allow surface oxide scale formation, and deforming the sample in tension at 5 s⁻¹ strain rate to 40% elongation or to fracture. Tests were conducted at temperatures 1000, 1100, 1200 and 1300°C. Low strain-rate tests at 0.005 s⁻¹ were also conducted at 1100°C. At least 2 samples were tested for each steel at each test temperature.

Surface hot shortness was assessed by evaluation of the extent of surface crack formation, i.e. by digital-imaging system measurement of the number of surface cracks and the perpendicular depth of each crack from the sample surface on the two sides of a 10 mm long metallographic section of the sample gauge length. These data were analyzed in terms of (i) average crack depth and (ii) crack density distribution relative to crack depth. Sample sections also were examined by scanning electron microscopy (SEM) to study the composition and morphology of the oxide scale and the oxide/metal interface.

2.4 SCALE FORMATION AND ADHERENCE

The study of scale formation and adherence was focussed on four medium-carbon (0.20 wt % C) steel compositions including the base composition levels and combinations of higher Si, high residual Cu, medium residual Sn and high residual Ni; and five low-carbon (0.04 wt % C) steel compositions including the base composition levels and combinations of higher Si, high residual Cu, medium residual Sn, high residual Ni and high P. The residual levels of Cu and Ni were higher in the medium-carbon steels than in the low-carbon steels.

Sheet samples of the hot-rolled steels were surface-machined and cut into pieces of dimensions 30 mm x 20 mm x 5 mm thick for the scale growth tests, and 165 mm x 37 mm x 5 mm thick for the scale adherence tests. Final surface preparation of the test samples entailed polishing with 40-grit paper to a uniform finish, ultrasonic cleaning in ethanol, and air-drying.

Scale growth tests were conducted by thermogravimetric analysis (TGA) using a high-precision digital-recording microbalance and a vertical tube furnace. The test entailed microbalance suspension of the sheet test sample in nitrogen atmosphere in the test temperature zone of the furnace reaction tube, allowing the sample to attain thermal equilibrium at test temperature for 10 min, then introducing the reaction gas (dry or moist air) to the reaction tube, and recording the weight increase of the sample during the oxidation reaction period of one hour. Scale growth tests were done in dry air and in moist (60% H₂O) air atmosphere at temperatures of 1000, 1100 and 1200°C for a reaction period of one hour. Two samples of each steel were tested for each oxidation test condition. The weight-increase data from the tests were analyzed with respect to reaction time and in terms of total weight increase during one hour of oxidation. Sample sections were examined by scanning electron microscopy (SEM) to characterize the composition and morphology of the oxide scale and the oxide/metal interface.

Scale adherence tests were performed by reacting the sheet test samples in a vertical tube furnace, subsequently removing the oxidized sample from the furnace and immediately positioning and deforming it in a bend-test device, and evaluating the amount of adherent scale on the tested sample. The test procedure involved suspension of the sheet sample in nitrogen atmosphere in the test temperature zone of the furnace reaction tube, allowing the sample to attain thermal equilibrium at test temperature for 10 min, then introducing the reaction gas (dry or moist air) to the reaction tube allowing the sample to oxidize for a period of one hour, and finally quickly removing the sample to the bend test (10 kg drop-weight from 600 mm height). Two samples of each steel were tested for each oxidation test condition: in dry air and in moist (60% H₂O) air atmosphere at temperatures of 1000, 1100 and 1200 °C for a reaction period of one hour. The amount of adherent scale on each tested sample was evaluated by (i) lightly tapping the bent sample, after it had cooled, to remove any loose oxide scale, (ii) weighing the sample with the remaining adherent scale, (iii) thoroughly cleaning the remaining adherent scale from the sample using a steel brush, (iv) weighing the cleaned sample, and (v) from the weight difference evaluating the weight of adherent scale per unit surface area of the sheet sample.

2.5 MECHANICAL PROPERTIES

The study of mechanical properties investigated three medium-carbon (0.20 wt % C) steel compositions including the base composition levels and combinations of high residual Cu, medium and high residual levels of Sn, and high residual Ni; and five low-carbon (0.04 wt % C) steel compositions including the base composition levels and combinations of medium and high residual levels of Sn, high residual Ni, high P, and higher levels of Si and Mn in the case of the plate composition. The residual level of Ni was higher in the medium-carbon steel than in the low-carbon steel.

For the mechanical properties study, equal lengths of hot-rolled steel plate were taken for machining of test samples: one length in the as-hot-rolled (HR) condition, and one length was given a step-cooling heat treatment (SC) to maximize grain boundary segregation of residual elements. The step-cooling treatment consisted of 595°C/1 h + 540°C/15 h + 525°C/24 h + 495°C/48 h + 470°C/72 h in an air-atmosphere furnace, with 0.9°C/min cooling between each step and furnace-cooling to room temperature after the final step. Tensile and Charpy test samples were machined from both the hot-rolled plate and the step-cooled plate for each steel of the study. Tensile test samples with gauge diameter of 8 mm and gauge length of 51 mm were taken transverse to the plate rolling direction and from the mid-thickness and mid-width part of the plate. Charpy test samples, 10 mm x 10 mm x 55 mm long, were taken transverse to the plate rolling direction and from the mid-thickness and mid-width part of the plate, and were notched parallel to the plate thickness direction.

Tensile data were obtained from testing of three tensile samples for each steel/condition. Three Charpy samples were impact-tested for each of a series of test temperatures for each steel/condition to generate absorbed energy transition curves and to determine ductile-to-brittle fracture transition temperatures (TT). Microstructural characterization of each steel/condition entailed optical metallographic determination of average ferrite grain size and pearlite volume fraction at ¼-thickness of plate sections. Fracture surfaces of selected Charpy-tested samples were examined by scanning electron microscopy (SEM). Auger electron spectroscopy (AES) analysis for grain boundary segregation was conducted on fracture surfaces of in-situ-tested samples machined from selected SC-condition samples. Auger sample dimensions were 3 mm dia x 20 mm long with a 1mm-deep circular groove machined at 9 mm from one end.

3. RESULTS

The summary of results given in the following for the four parts of the experimental study illustrate and describe non-proprietary examples only of the total results.

3.1 HOT DUCTILITY

3.1.1 Medium-Carbon Steels

Gleeble test results for the medium-carbon base-composition steel M1 are presented in Fig. 1. The percent reduction-of-area (RA%) versus deformation temperature curve shows the typical ductility trough with minimum at 750°C. The ductility trough minima for all medium-carbon steels M1-M6 were in the

800-700°C temperature range. In general, additions of Cu and/or Sn to the base composition increased ductility loss, whereas addition of Ni to steels containing Cu and Sn counteracted the increase in ductility loss. The maximum load versus deformation temperature curve in Fig. 1 shows a reduction in slope of the curve with decreasing temperature at 800°C, an indication that the equilibrium start-temperature for the austenite-to-ferrite transformation, A_{e3} , is at 800-750°C. In general, the A_{e3} for all medium-carbon steels M1-M6 fell in this temperature range. Ductility loss below A_{e3} is caused by the formation a thin film of ferrite along austenite grain boundaries. Optical metallography of quenched Gleeble samples from the 600°C test temperature confirmed the presence of proeutectoid grain-boundary ferrite.

Fractured Gleeble samples of the base-composition steel M1 are shown in Fig. 2. Figure 3 presents the SEM images of the fracture surfaces in relation to key points on the ductility curve for steel M1. Typically, steels exhibited high ductility at 1000°C with fully ductile transgranular failure. Between 800 and 700°C, failure morphology was typically intergranular with a local ductile fracture appearance in the form of microvoid coalescence on the intergranular facets, e.g. Fig. 4. Improved ductility at 600°C was characterized by a significantly decreased amount of intergranular fracture.

An example of energy-dispersive X-ray analysis (EDX) carried out to identify particles which may have contributed to the low-ductility intergranular fracture (ductility trough) is shown for the small Mn sulphide particle (indicated by arrow in Fig. 4) on the M1 (700°C) fracture surface. EDX analysis on polished sections near the fracture surface revealed a distribution of (Mn) and (Mn, Fe) sulphide particles along grain boundaries. In steel M3 containing residual Cu, Sn and Ni, evidence of Cu and Sn segregation at the MnS particles was observed. AES analysis on fracture surfaces of in-situ-tested samples of residual-containing steels, which had been quenched from the Gleeble test maximum-load condition, revealed significant enrichments of Cu and Sn, indicative of grain-boundary segregation and embrittlement.

3.1.2 Low-Carbon Steels

Gleeble test results for the low-carbon base-composition steel L1 presented in Fig. 5 show the ductility trough minimum at 850°C in the RA% vs. temperature curve, and the A_{e3} transformation start-temperature in the 900-850°C range in the maximum load vs. temperature curve. In general, the ductility minima for all low-carbon steels L1-L7 were in the 900-800°C range, most occurring at 850°C, and the A_{e3} temperatures were in the 900-850°C range. The addition of Cu, Sn or P to the base composition decreased ductility and lowered the ductility trough. Addition of combinations of these elements did not further reduce ductility. Addition of Ni, in equal amount to Cu, to steels containing Cu and Sn did not improve ductility.

Fractured Gleeble samples of the base-composition steel L1 are shown in Fig. 6, and low and high SEM magnifications of sample fracture surfaces are shown in Figs. 7 and 8, respectively. High ductility at 1000°C is characterized by fully ductile transgranular failure, minimum ductility at 850°C is characterized by extensive intergranular failure [Fig. 7(b)] with localized ductile morphology on intergranular facets [Fig. 8(b)], and high ductility at 750°C is characterized by generally transgranular ductile morphology. These characteristic failure morphologies of the three ductility regions were generally typical of all low-carbon

steels L1-L7.

Neither EDX analysis of fracture surfaces in the scanning electron microscope, nor AES analysis of in-situ-fractured samples, found any evidence of segregation of residual elements related to intergranular embrittlement failure in the low-carbon steels. Optical metallography of Gleeble samples quenched from the 600°C test temperature revealed proeutectoid grain-boundary ferrite as shown for steel L2 in Figure 9.

3.2 SURFACE HOT SHORTNESS

3.2.1 Medium-Carbon Steels

Examples of the surface crack measurement results for the medium-carbon steels M1-M6, after tensile testing to 40% elongation at 1100°C and 5 s⁻¹ strain rate, are the average crack depth data in Fig. 10 and the crack depth distributions graphed in Fig. 11. It can be seen that, although the average depth data (Fig. 10) indicates the relative severity of hot shortness cracking for each steel, it does not reveal distribution of cracks in terms of depth magnitude and density as shown in Fig. 11. In general, deep crack development was present at 1000 and 1100°C test temperatures when residual Cu content exceeded Ni content, and was absent at 1200 and 1300°C test temperatures. Crack depth decreased significantly at the higher test temperatures 1200 and 1300°C. Crack depth at the 1100°C test temperature increased and crack density decreased when tensile strain was lowered to 0.005 s⁻¹.

Examples of deep surface cracks are illustrated in the SEM micrograph of steel M6 in Fig. 12. The EDX spectra in Fig. 12 revealed segregation of Cu and Ni at the tip and along the path of the crack, as well as at steel surface grain boundaries and at the steel/oxide interface.

3.2.2 Low-Carbon Steels

Examples of average crack depth data and crack depth distributions are shown in Figs. 13 and 14, respectively, for the low-carbon steels L1-L7, after tensile testing to 40% elongation at 1100°C and 5 s⁻¹ strain rate. These data clearly indicate that the average crack depth data (Fig. 13) alone are inadequate to reveal the incidence of deep cracks for steels L6 and L7 (Fig 14). In general, the combined addition of residual Cu and Sn, regardless of the presence of the Ni addition, resulted in the development of deep surface cracks at 1000 and 1100°C test temperatures, and this was significantly decreased at 1200 and 1300°C. Crack depth generally decreased with increase of test temperature to 1200 and 1300°C, and did not appear to increase with decrease of strain rate at the 1100°C test temperature. SEM examination generally revealed no residual metal deposits in the vicinity of the steel/oxide interface.

3.3 SCALE FORMATION AND ADHERENCE

3.3.1 Scale Growth

3.3.1.1 Medium-carbon steels

An example of weight increase data (weight increase per unit surface area) obtained in scale growth tests is shown in Fig. 15 for medium-carbon steels M1, M7-M9 oxidized at 1200°C in dry air atmosphere. From these data, oxidation rate constants and total weight increase during one hour of oxidation were determined. An example of total weight increase data for one-hour oxidation of steels M1, M7-M9 at 1200°C is shown in Fig. 16 for both dry and moist air atmospheres. In general, variations in oxidation rate and in total weight increase did not correspond with residual levels in steels. However, as indicated in Fig. 16, introduction of moisture to the oxidation atmosphere significantly increased growth rate and total weight of oxide scale. Figure 17 shows the effect of oxidation temperature on total weight increase for one-hour oxidation of steels M1, M7-M9 in moist air atmosphere. Increase of oxidation temperature was consistently found to increase oxide scale formation.

SEM images of cross-sections of oxide scale are illustrated in Fig. 18 for steels M7 and M9 oxidized one hour at 1200°C in dry air. The scale consists of an outer thin layer of hematite (Fe_2O_3), an intermediate layer of magnetite (Fe_3O_4) and an inner layer of wustite (FeO). The dark gap in the wustite layer is the result of separation in the scale during cooling after the oxidation test. EDX analysis revealed that the innermost part of the wustite layer, which remained adherent to the steel substrate, includes embedded metallic deposits of Ni, Cu and Fe in the residual-containing steel M9, and also includes Si (iron silicate) compounds in those steels containing the higher level of Si. Scale formed in moist atmosphere generally featured increased porosity in the inner layers, shown for steel M9 in Fig. 19.

3.3.1.2 Low-carbon steels

The scale growth observations on the low-carbon steels generally were similar to those on the medium-carbon steels. Weight increase data for one-hour oxidation of steels L1, L4, L7, L8 at 1200°C shown for dry and moist atmospheres in Fig. 20 exemplify increased scale formation in moist atmosphere. The effect of increased scale growth as a result of increasing oxidation temperature is shown in Fig. 21 for steels L1, L4, L7-L9 oxidized for one hour in moist atmosphere.

In the residual-containing low-carbon steels, a very small amount of Ni and Cu metallic deposits were formed in the inner scale layer near the steel substrate, compared to the medium-carbon steels. However, Si (iron silicate) compounds were formed in this inner layer on the steels containing the higher level of Si. Increased porosity developed in the inner scale layers formed in moist atmosphere.

3.3.2 Scale Adherence

3.3.2.1 *Medium-carbon steels*

Scale adherence was measured in terms of the weight of remaining adherent scale per unit surface area of steel sample after deformation in the bend test. Results generally showed that introduction of moisture in the oxidizing atmosphere dramatically increased scale adherence. This effect is shown in Fig. 22 for medium-carbon steels M1, M7-M8 oxidized for one hour at 1200°C. It was also generally observed that scale adherence increased with increasing oxidation temperature, as indicated in Fig. 23 for steels M1, M7-M9 oxidized for one hour in moist atmosphere. Residual-containing steels M8, M9 exhibited higher scale adherence at the higher oxidation temperatures 1100 and 1200°C, particularly in moist atmosphere. The higher level of Si (0.3%) in the steel did not consistently increase scale adherence.

3.3.2.2 *Low-carbon steels*

Scale adherence on the low-carbon steels was much lower and results were less consistent than on the medium-carbon steels. This difference can be seen in Figs. 24 and 25 when compared with Figs. 23 and 22 for the medium-carbon steels. Figure 24 presents the scale adherence relative to oxidation temperature, and Fig. 25 presents the scale adherence relative to oxidizing atmosphere at 1200°C, on steels L1, L4, L7-L9. In general, scale adherence did not correspond consistently with Si content or residual content in the low-carbon steels.

3.4 MECHANICAL PROPERTIES

3.4.1 Medium- and Low-Carbon Steels

Addition of residuals in both medium- and low-carbon steels in the hot-rolled (HR) condition decreased ferrite grain size by up to 29%, but had little effect on volume fraction of pearlite. Pearlite volume fraction was approximately 8X larger in the medium-carbon steels than in the low-carbon steels. The step-cooling heat-treatment (SC) was expected to effect little change on these microstructural characteristics.

Example tensile stress-strain curves are shown in Fig. 26 for low-carbon steels L1 (base) and L12 (with residuals). Both low- and medium-carbon steels in both hot-rolled (HR) and step-cooled heat-treated (SC) conditions exhibited discontinuous yielding behaviour. Yield strength (YS) and ultimate tensile strength (UTS) generally increased slightly with increasing residual content in both medium-carbon (Fig. 27) and low-carbon (Fig. 26) steels. Yield and ultimate tensile strengths were decreased slightly by the step-cooling (SC) treatment (e.g. Fig. 28). The Charpy curves in Figs. 29 and 30, respectively, show slight increases of transition temperature (40 J temperature) in residual-containing hot-rolled (HR) medium-carbon and low-carbon steels. The ductile-to-brittle transition occurs very abruptly in the low-carbon steels, with the transition of the plate composition steel L13 located 80°C lower than the strip steel compositions L1, L10-12 (Fig. 30). The step-cooling heat-treatment (SC) had the effect of increasing the 40 J transition temperature by up to 24°C for steel M3 (Fig. 31) and up to 28°C for steel L13 (Fig. 32).

SEM examination of Charpy fracture surfaces of the L13 steel tested at liquid N₂ (-196°C) temperature revealed approximately 6% intergranular fracture for the HR condition and 20% intergranular fracture for

the SC condition (Fig. 33). AES spectroscopy of an in-situ-test fracture surface of steel L13(SC), for example, revealed Sn enrichment (spectra in Fig. 35) on a fracture (grain boundary) facet (spot 2 in Fig. 34). Similar AES observations were made on medium-carbon steel M3(SC).

4. DISCUSSION

4.1 HOT DUCTILITY

The hot ductility curve, percent reduction of area (RA%) vs. deformation temperature, represents three characteristic ductility regions as illustrated in Fig. 36. If a critical RA% below which embrittlement (intergranular fracture) occurs is defined by R1, then the temperatures T1 and T2 at the R1 intercepts on the hot ductility curve define the ductility trough, i.e. the embrittlement region. The low-temperature-high-ductility and the high-temperature-high-ductility regions are below temperature T1 and above temperature T2, respectively.

The literature survey conducted for this experimental study described the deformation/fracture mechanisms for the three ductility regions. In the high ductility region at temperatures above T2, deformation proceeds in relatively low flow-stress, high recovery-rate, single-phase austenite, leading to ductile transgranular fracture.

In the high temperature end of the ductility trough region, precipitates such as MnS and AlN form preferentially at grain boundaries leaving a soft precipitate-free zone around the grain boundaries, and thus plastic deformation concentrates along the grain boundaries. The precipitates at the grain boundaries are sites for void formation and coalescence, giving rise to crack initiation and propagation along the grain boundaries and ultimately intergranular fracture. At lower temperature in the ductility trough (A_{e3}), ferrite begins to form preferentially at the grain boundaries. Ferrite with its higher recovery rate is softer than austenite, and thus allows concentration of plastic deformation along the grain boundaries. Again, the presence of precipitates in the concentrated strain path at the grain boundaries leads to embrittlement and intergranular fracture.

In the region at temperatures below T1, recovery to higher ductility is associated with the formation of a larger amount of ferrite, which removes the concentration of plastic strain at the grain boundaries and results in substantial decrease of intergranular fracture. Also, the strength (flow stress) differential between ferrite and austenite decreases with decreasing temperature, resulting in a more balanced accommodation of strain in the two phases.

Fractographic evidence, e.g. Fig. 3 for medium-carbon steel and Figs. 7 and 8 for low-carbon steel, is consistent with literature description of the three ductility regions. Metallographic observations of MnS particles at grain boundaries in medium-carbon steel (e.g. Fig. 4), and proeutectoid ferrite at grain boundaries in medium- and low-carbon steels (e.g. Fig. 9) are consistent with grain-boundary embrittlement and intergranular failure in the ductility trough region. Increased ductility loss in residual-containing medium-carbon steel could be related to observed segregation of Cu and Sn at MnS particles,

and at grain boundaries as observed in AES at intergranular fracture facets. The segregation of Cu and Sn at grain boundaries decreases ductility primarily by retardation of grain boundary movement and enhancement of void formation and coalescence at the boundaries. The observed effect of Ni addition to counteract the ductility-loss effect of Cu results from its ability to increase Cu solubility in austenite and thereby decrease Cu segregation to grain boundaries.

Comparison of hot ductility curves for the base-composition steels in Fig. 37 indicates that minimum ductility (in the ductility trough region) is decreased from 57% RA for the low-carbon steel to 32% RA for the medium-carbon steel, which primarily has higher level of C and also higher levels of Si and Mn. Also, the minimum ductility temperature is decreased from 850°C for the low-carbon steel to 750°C for the medium-carbon steel, mainly the result of the effect of higher C and Mn on lowering of the A_{e3} transformation temperature.

4.2 SURFACE HOT SHORTNESS

The conditions for hot shortness develop during high-temperature oxidation of the steel surface, as for example in reheating prior to hot working. Residual elements in steel, such as Cu, Ni and Sn, each have a role in surface hot shortness; among these Cu is the key element required for hot shortness to occur. Samples of two selected grades of steel with selected residual compositions were oxidized one hour at temperatures of 1000, 1100, 1200 and 1300°C and then deformed in tension at the oxidation temperature to test for susceptibility to surface cracking. The test results are discussed below in terms of the main factors affecting surface hot shortness.

One of the main factors is the rate of oxidation, which increases with temperature. At lower oxidation temperatures and lower rates of oxidation, the rate of metal consumed in oxide formation is low, and the rate of back diffusion of non-oxidizing residual elements into the steel is low. Consequently, a concentration of non-oxidizing elements will form in the steel surface layer and at the steel/oxide interface. Examples of this type of concentration leading to formation of deep surface cracks were observed at the lower oxidation temperatures, particularly as shown for 1100°C (steels M2, M4, M6 in Fig. 11, and steels L5, L6, L7 in Fig. 14). At higher oxidation temperatures and higher rates of oxidation, the steel surface will be consumed by oxidation at a higher rate, coupled with higher rate of back diffusion of non-oxidizing residual elements into the steel. Therefore, a concentration of the unoxidized residual elements will not be formed at the steel/oxide interface and the conditions for deep surface crack formation will be diminished. This result of higher oxidation rate was observed in the significant decrease or absence of deep surface cracks at the oxidation temperatures of 1200 and 1300°C.

Copper is the key constituent in the concentration of non-oxidizing elements at the steel/oxide interface, and ultimately in surface crack initiation. Copper in excess of its solubility in austenite forms a liquid Cu-rich phase at the steel surface which readily penetrates the surface grain boundaries. The presence of liquid Cu-rich phase greatly reduces the energy required for crack initiation at a surface grain boundary, and the favourable wettability of Cu with austenite allows it to wet the propagated crack surface and enhance crack deepening. An example of this effect of Cu on deep crack formation is shown in the SEM

micrograph, Fig. 12, for steel M6 tested at 1100°C.

The residual element Sn alone does not cause surface cracking; however, it effectively enhances the effect of Cu in formation of surface cracks by decreasing the solubility of Cu in austenite. The results of this work confirmed this combined effect of Sn and Cu in the observation of deeper surface cracks in both the medium- and low-carbon steels.

Additions of Ni have the reverse effect by increasing the solubility of Cu in austenite, and also by increasing the melting point of the Cu-rich phase concentrated at the steel surface. By increasing the melting point and the solubility of Cu, Ni when present in sufficient amount prevents the liquation of the Cu-rich phase concentrated at the steel surface and thereby suppresses surface crack formation. Calculated solubility limits of Cu in the Fe-Cu-Ni system indicate that, when the ratio $\text{Ni/Cu} = 1$, the Cu solubility limit in austenite is significantly increased. When the ratio $\text{Ni/Cu} < 1$, Cu solubility in austenite is reduced and the formation of a liquid Cu-rich phase is unavoidable. Published literature has reported $\text{Ni/Cu} = 0.5$ will suppress the detrimental Cu effect when no Sn is present, and $\text{Ni/Cu} = 1$ is required when an intermediate residual level of Sn is present. In the present work, the ratio $\text{Ni/Cu} = 1$ was found to be adequate in medium-carbon steel with intermediate residual level of Sn, but not with combined higher residual levels of Cu and Sn, and was found to be inadequate in the low-carbon steel.

The effect of higher Si level (0.3%) in the medium-carbon steels is to contribute to the suppression of surface crack formation at the higher test temperatures above 1100°C. Silicon, more reactive with oxygen than iron, oxidizes internally with oxygen diffusion through metal-matrix paths, and forms local oxides of iron silicates (fayalite Fe_2SiO_4) in the steel subsurface. Fayalite melts eutectically with FeO at 1177°C and acts as a trap for the Cu-rich phase which normally concentrates at the steel/oxide interface. The fayalite tends to undermine the Cu-rich phase and, because it oxidizes preferentially, effectively entangles and transports the Cu-rich phase into the oxide scale.

Phosphorus has been reported to promote internal cracking when level exceeds 0.03 wt %. Low-carbon steel containing a higher level of P in the present work exhibited some deeper surface cracks at 1200 and 1300°C. This result would be caused by increased segregation of P to surface grain boundaries at the higher temperatures.

The decrease of strain rate to 0.005 s^{-1} in the 1100°C tests on medium-carbon steels resulted in the development of fewer, but deeper surface cracks. The interpretation of this result is that fewer cracks were initiated because cracks had time to propagate to greater depth at the lower strain rate.

4.3 SCALE FORMATION AND ADHERENCE

4.3.1 Scale Growth

In this study, changes in oxide growth rate were more pronounced with changes in oxidation temperature and in furnace atmosphere than with changes in steel residual composition. The following discussion addresses these main factors affecting oxide scale growth.

Oxidation rate is a function of time and temperature. Generally, the rate is either a linear relationship with time, or parabolic. Linear oxidation is controlled by the diffusion rate of oxygen atoms from the bulk of the furnace gas to the reaction surface, i.e. it is a gas-phase-controlled process, and normally occurs during the initial stage of the oxidation period. Parabolic oxidation is a diffusion-controlled process by the rate of outward diffusion of metal ions and/or the rate of inward diffusion of oxygen ions through the oxide layer. Oxidation usually proceeds parabolically after the oxide layer reaches a certain thickness. Oxidation rates were parabolic for most of the tests on the medium-carbon steels and for 2/3 of the tests on the low-carbon steels in this study. Parabolic oxidation rate increases with increasing temperature according to an Arrhenius relationship:

$$K_p \propto 1 / \exp (1/T) .$$

The results of this study, as exemplified in Figs. 17 and 21, generally exhibited increased oxide scale growth with increase of temperature.

The experimental results showed no clear dependence of the magnitude of oxidation rate on residual composition of the steels. As described in Section 4.2 for surface hot shortness, residual levels of Cu and Ni result in effects at the steel/oxide interface rather than on oxide scale formation. In the case of the residual-containing medium-carbon steels, metallic deposits of Cu and Ni were shown embedded in the inner scale layer at and near the steel substrate (e.g. steel M9, Figs. 18 and 19), however these deposits were finely dispersed and would not act as a significant diffusion barrier in the oxidation process.

Oxide growth rates increased significantly when moisture was introduced to the oxidation atmosphere (Figs. 16 and 20). This moisture effect is suggested in the literature to be related to porosity in the oxide scale. As the oxide scale thickens, compressive stresses develop in the scale because the volume of oxide product is larger than the corresponding volume of iron substrate to which the oxide adheres. The buildup of compressive stress during scale growth leads to plastic deformation and the formation of cracks, channels and voids in the scale. It has been suggested that moisture (steam) entering the oxide scale enhances plastic deformation and creep in the scale, and thus increases porosity particularly in the inner scale layer to relieve compressive stresses. While pore gaps in the scale normally disrupt the diffusion process of oxide formation, the filling of the pores by H₂O and H₂ provides a mechanism of transport of oxygen across the pore gaps at rates faster than the rates of outward diffusion of iron in the solid scale.

4.3.2 Scale Adherence

Oxide scale adherence can be affected, in general, by the same factors as for scale growth, i.e. oxidation temperature, oxidation atmosphere and steel composition.

The increase in scale adherence with increase of oxidation temperature on bend-tested samples of the medium-carbon steel, as shown for example in Fig. 23, can be related to plasticity behaviour of the oxide scale. Scale plasticity increases with increasing temperature, leading to increased formation of pores and voids, particularly in the inner part of the scale near the steel substrate. The increased plasticity and resulting porosity effectively relieve compressive stresses resulting from the interatomic volume difference between the oxide scale and the steel substrate and enhance interface bonding of the scale to the substrate.

Increased scale adherence also was observed when moisture was added to the furnace oxidizing atmosphere, as shown in Fig. 22 for the medium-carbon steels oxidized at 1200°C. As discussed for scale growth above, moisture (steam) entering the oxide scale enhances scale plasticity and creep behaviour and increases porosity, particularly in the inner part of the scale near the steel/scale interface (e.g. steel M9 in Fig. 19). These effects provide further relief of the compressive stress in the scale and increase the scale-to-steel bond at the interface.

Additions of Ni and Cu have less affinity for oxygen than Fe and concentrate at the steel/oxide interface during oxidation. Combined Ni and Cu additions in medium-carbon steels resulted in the formation of a more irregular steel/oxide interface and metallic deposits of Ni and Cu compounds embedded in the inner scale layer at and near the interface (e.g. steel M9 in Figs. 18 and 19). The irregular interface and embedded filament-like deposits effectively increased scale adherence, particularly at the 1100 and 1200°C oxidation temperatures.

The higher level of Si in the steels increased scale adherence in some cases, but this effect did not occur consistently. Observation of increased adherence has been attributed by others to effects of the Si addition toward lowering the compressive stresses developed in the inner scale layer during scale growth. This has been reported to take place by two mechanisms. Silicon oxidizes preferentially to form an iron silicate (fayalite) which becomes molten at the higher oxidation temperatures and can act to relieve stresses in the inner scale layer. Also at the higher oxidation temperatures, the formation of gaseous Si oxides could contribute to increased porosity in the inner scale layer which leads to stress relief and enhances adherence of the scale.

The above effects described for the medium-carbon steels were observed less consistently on the low-carbon steels, primarily because the amount of adherent scale was much lower on the low-carbon steels.

4.4 MECHANICAL PROPERTIES

The metallographic observation of decrease in ferrite grain size with increasing residual content is supported by evidence in the literature that Cu and Sn additions retard austenite recrystallization, and Cu

also retards austenite-to-ferrite transformation.

The increase of yield strength with increasing residual content (Figs. 26 and 27) is related to the effects of Sn addition, primarily on ferrite grain refinement, and secondarily on solid solution hardening of the ferrite. The softening after step-cooling heat-treatment (e.g. Fig. 28) is consistent with a degree of recovery during the heat-treatment.

Comparison of 40J transition temperatures in Charpy curves (Fig. 30) for the base-composition low-carbon steel L1 with steels L10-L12 in the hot-rolled condition indicates that the addition of residuals had little effect. However, higher levels of Mn and Si in the plate-composition steel L13 lowered the 40J transition temperature by 80°C and increased upper shelf energy (Fig. 30). This improvement of Charpy impact properties is associated mainly with the higher level of Mn through its effects of increasing solid solution hardening, pearlite content and ferrite grain refinement. The step-cooling heat-treatment raised the 40J transition temperature of steel L13 by 28°C (Fig. 32). The magnitude of this embrittlement effect from heat-treatment-induced grain boundary segregation of residual Sn is considered to be limited by the inhibiting effect of C competing for grain boundary sites. In heat-treated steels L10-L12, residual additions had no embrittling effect in the absence of the higher Mn and Si levels.

Additions of residual elements in the medium-carbon steels (all containing the higher levels of Mn and Si) in the hot-rolled condition produced only small increases in 40J transition temperature (Fig. 29). The limited moderate increase of 40J transition temperature resulting from heat-treatment-induced grain boundary embrittlement (Fig. 31) can be attributed to the inhibiting effect of C competing with segregating Sn for grain boundary sites.

Comparison of the Charpy transition curves for the two grades of hot-rolled steel (Figs. 29 and 30) shows the typical gradual transition with temperature in the medium-carbon steels, and a very abrupt transition in the low-carbon steels. The abrupt transition behaviour, Fig. 30, is typical of low-carbon steels. However, the 40J transition temperatures in Fig. 30 are not as low as usually found in low-carbon steels because of the larger ferrite grain size developed from the high finish-rolling temperature in the processing of the steels for this study.

Carbon is believed to segregate significantly and to limit or prevent embrittlement by strengthening grain boundary cohesion and by inhibiting segregation of embrittling elements. The increases in 40J transition temperature shown for heat-treated steels L13 and M3 in Figs. 32 and 31 are consistent with the generally accepted view that grain boundary segregation of residuals decreases as carbon level increases. In general, this study indicates that only limited grain boundary segregation of residuals occurs in the low- and medium-carbon steels and that this segregation requires the presence of alloy elements such as Mn and Si.

4.5 RELEVANCE TO THE STEEL INDUSTRY

4.5.1 Hot Ductility

The results of this study relate to avoidance of problematic transverse cracking in continuous-casting processes. The results provide information on RA% (engineering strain), deformation temperature, and steel residual composition for the steel grades and residual compositions chosen by the participating steel companies. This information was quantified in reference to the three hot ductility regions defined in Fig. 36. In a continuous-casting process, the value of R1, the critical RA%, is not known exactly, but can be determined from the magnitude of applied deformation and the strand thickness. Considering a critical RA of 60%, the upper and lower critical temperatures, T2 and T1, and the ductility trough area were determined from the ductility curve for each steel. A new dimensionless factor, the Relative Trough Area (RTA), was defined as

$$\text{RTA} = \frac{\text{trough area of a specific residual-containing steel}}{\text{trough area of the base-composition steel.}}$$

The values of RTA, T2 and T1 were determined for the steels in both the medium- and the low-carbon series, and the steels in each series were ranked according to RTA value.

During continuous casting, transverse cracking will occur if the deformation of the strand shell is greater than that in the ductility curve. In relation to Fig. 36, a region in the slab with temperature between the critical temperatures T2 and T1 is susceptible to cracking. Therefore, straightening of the strand should be done on the hot side above T2 or on the cool side below T1. The critical T2 and T1 values for the residual-containing steels provide a useful guide for control of the continuous-casting process relative to residual content.

The results of the present study also provided guiding information on the amount of Ni addition required to effectively counteract the negative effects of Cu and Sn in decreasing ductility. Of particular significance, the study confirmed that Sn and Cu influence hot ductility individually, unlike the case of surface hot shortness where Sn is effective only in the presence of Cu, i.e. Sn intensifies the effect of Cu on hot shortness, and without Cu it has no effect.

4.5.2 Surface Hot Shortness

The results of the surface hot shortness study relate to surface crack formation during reheating and hot-rolling processing of steel produced from residual-containing recycled scrap charge. The conditions for surface hot shortness are developed during the formation of oxide scale on the steel surface in the oxidizing atmosphere of the reheating furnace. During reheating, iron is removed from the steel surface layer by oxidation in preference to more noble residual elements such as Cu, Sn, Ni and Sb. Consequently, the oxidation process can result in concentration of these non-oxidizing residual elements in the steel surface layer and at the steel/oxide interface. The element Cu is essential for surface hot shortness; without it, surface hot shortness does not occur. Copper can enrich to a level exceeding its

solubility in austenite and form a liquid Cu-rich phase which can easily penetrate the surface austenite grain boundaries. Under hot-working strain such as hot-rolling, surface cracks are easily formed at the liquid-filled surface boundary sites. Other residual elements Sn and Sb enhance the detrimental effect of Cu by decreasing the solubility of Cu in austenite, whereas Ni counteracts the Cu effect by increasing the solubility of Cu in austenite and increasing the melting point of the Cu-rich phase.

Reheating temperature is an important factor through its effect on the rate of oxidation. Results of the present study on both medium- and low-carbon steels showed that surface cracking was most severe at 1100°C, less at 1000°C, and substantially less at 1200 and 1300°C (these results were explained in section 4.2). With the trend of recent practice to reheat at lower temperatures to control austenite grain size and to reduce energy consumption, there is greater risk of surface cracking in residual-containing steels, and residual composition becomes more critical.

Experimental results also demonstrated limitations on the validity of published Cu-equivalent and Ni/Cu-ratio formulae for the addition of Ni to suppress surface cracking. In the case of the medium-carbon steels in this study, the recommended Ni addition was inadequate for combined high Cu and high Sn residual levels, and in the low-carbon steels the recommended Ni addition was inadequate for combined high Cu and intermediate Sn levels.

Presentation of measured crack depths in terms of the depth distribution of crack density (number of cracks per length of sample surface) indicated the residual compositions and the oxidation temperatures for which deep cracks were formed and the incidence (density) of deep crack formation.

In general the results provided, within the scope of the experimental program, guideline data on acceptable residual levels that would not result in deep surface crack formation in the selected grades of steel.

4.5.3 Scale Formation and Adherence

The main implications of the study of scale formation and adherence on reheating and hot-rolling of steel are found in the results of the scale adherence tests. When steel exits from the reheat furnace, it is desirable that the oxide scale formed in the reheat can be removed from its steel substrate easily and completely, leaving a clean steel surface. The scale adherence tests indicate that increasing reheat temperature (Fig. 23) and introducing moisture in the reheat furnace atmosphere (Fig. 22) would adversely increase adherence. The addition of Ni to beneficially counteract the detrimental effect of Cu on surface hot shortness also would have the adverse effect of increasing scale adherence, particularly at typical reheat temperatures 1100-1200°C. Similarly, higher levels of Si can increase scale adherence at reheat temperatures. The adverse scale adherence effects noted here were found to be more consistent and prominent on the medium-carbon steels, and less so on the low-carbon steels.

4.5.4 Mechanical Properties

The results of the study of mechanical properties relate to the effects of steel composition (C, Mn, Si, P,

and residual elements), to the effects of microstructure (ferrite grain size, pearlite volume fraction), and to the effects of heat treatment (to maximize grain boundary segregation). The results provided guideline information on mechanical properties relative to the steel compositions selected for this project. Also, the results gave indication of how the microstructure developed in reheating and hot-rolling processing of the steel can affect its mechanical properties. Embrittlement effects of residual segregation in the as-hot-rolled steels were small and should not cause serious problems in practice.

4.6 RELEVANCE TO ENERGY/ENVIRONMENT

The intent of this study on effects of residuals in carbon steels is to provide information which will help steel companies to increase the use of recycled scrap steel in the production of modern grades of steel. Recycling of steel scrap in steelmaking not only conserves virgin material resources, but also reduces the amount of waste material. Steel has high recyclability, estimated at 44% recycling rate [1] and as high as 70% in Japan [3]. In United States, approximately 60-65 million tons of scrap iron and steel are recycled each year, representing approximately 50% of new steel production [4]. Recycling of steel has its major benefit in reduced energy consumption; steel production from scrap charge requires 74% less energy than production from virgin ore material [4,5].

Reduction in energy consumption has direct environmental benefit. Carbon dioxide (CO₂) constitutes approximately 85% of manmade greenhouse gas (GHG) emissions, and almost all of manmade CO₂ emissions come from production of energy by fossil fuel combustion [6]. In 1994, the industrial sector generated approximately 35% of energy-related CO₂ emissions, and the iron and steel industry accounted for approximately 14% of this amount, i.e. almost 5% of energy-related CO₂ emissions [6, 7]. Scrap-based steelmaking, less energy intensive than integrated steelmaking primarily due to its extensive use of scrap metal, generates only a small fraction of the total iron and steel industry CO₂ emission [6]. In 1995, EAF steelmaking produced 40% of the 95 million ton total steel production in United States, but generated only 20% of the CO₂ emissions from the iron and steel industry because of its lower energy consumption [6]. Thus, an integrated steelmaking process represents up to 3 times the CO₂ emission than that from an EAF process.

EAF steelmaking has experienced steady growth over the past three decades in North America, from 15% of total steel production in 1970 to 40% in 1995 [5], and to approximately 50% in 2001 [8]. Almost all EAF mills use 100% scrap charge, and on average BOF mills use at least 25% scrap charge. The growth in use of recycled scrap steel was a significant factor in the more than 20% reduction in energy intensity of steelmaking (energy consumption per ton of steel) in United States between 1971 and 1994 [5,7]. One of the policies cited [7] to help industry reduce energy consumption and CO₂ emission efficiently without loss of domestic productivity is that of increasing the potential for scrap-based production.

Scrap-charged EAF steelmaking has had significant production cost advantage over traditional integrated mill practice, primarily in commodity long-product markets, and more recently in flat-rolled products [8]. While it has been estimated that 75% of hot-strip product can be made using scrap-charged EAF steelmaking [1], the development of this technology has not yet advanced to the capability of producing

grades with high quality specifications, such as IF steel for exterior automotive body panel application. Nevertheless, scrap-based steelmaking technology is continuing to evolve towards production of higher quality steel grades. Steel plate with high-strength, high-toughness specifications for linepipe application is competitively produced from scrap-charged EAF processing.

Current information on the production cost advantage of scrap-based steelmaking compared with integrated steelmaking is difficult to obtain. One current reference [1] indicates that EAF plant processing of galvanized and tin-plated strip products can have 20-120 U.S.\$/ton advantage over integrated plant processing. Ascription of the cost savings to scrap metal charge and to reduced energy consumption was not specified.

The results of the present study provide information on effects of selected residual compositions and processing parameters on properties of selected medium-carbon and low-carbon steel grades which steel companies can apply to design of steel furnace-charges, processes and products, utilizing recycled scrap steel with the ensuing benefits of reduced energy consumption, reduced cost and environmental compliance.

5. CONCLUSIONS

5.1 HOT DUCTILITY

5.1.1 Medium-Carbon Steels

- Additions of Cu and Sn at the levels of this study decrease hot ductility; addition of Ni at the levels of this study to Cu- and Sn-containing steels improves ductility.
- Ductility trough minima occur at 800-700°C, and equilibrium transformation temperature A_{e3} occurs at 800-750°C.
- All of the steels studied have fully ductile transgranular failure at high temperatures ($>1000^{\circ}\text{C}$), and at the minimum ductility temperatures failure morphologies are typically intergranular with local ductile fracture appearance on the intergranular facets.
- Fine (Mn) and (Mn, Fe) sulphide particles along grain boundaries are responsible for ductility loss and intergranular failure; Cu and Sn segregation observed at the MnS particles would enhance this embrittlement failure.
- A new factor, Relative Trough Area (RTA), is defined as a useful tool for comparing ductility curves and ranking the ductility of the steels. Associated with the critical ductility of the ductility trough, the upper (UCT) and lower (LCT) critical temperatures are defined. To avoid transverse cracking in a continuous-casting process, straightening deformation in the strand should be done at temperatures either above the UCT or below the LCT. Considering a critical reduction-of-area of 60%, critical

temperatures with relation to preventing transverse cracking were measured for the steels in this study

5.1.2 Low-Carbon Steels

- Additions of Cu and Sn and P at the levels of this study decrease hot ductility; addition of Ni at the level of this study to Cu- and Sn-containing steels does not improve hot ductility.
- Ductility trough minima occur at 900-800°C, and equilibrium transformation temperature A_{e3} occurs at 900-850°C.
- All of the steels studied have failure morphologies as described above for the medium-carbon steels, i.e. ductile transgranular failure at high temperatures (>1000°C) and embrittled intergranular failure at the minimum ductility temperatures.
- No enrichment or segregation of Cu or Sn was observed at the fracture surface in limited examination of the low-carbon steels.
- As described above for the medium-carbon steels, the low-carbon steels are ranked for ductility in terms of their RTA values, and critical temperatures (UCT and LCT) on the basis of 60% critical reduction-of-area were measured with relation to prevention of transverse cracking in a continuous-casting process.

5.2 SURFACE HOT SHORTNESS

5.2.1 Medium-Carbon Steels

- Copper addition in excess of Ni content, at the levels of this study, results in development of deep surface cracks at 1000 and 1100°C, but not at 1200 and 1300°C.
- Nickel addition in equal amount to Cu content, at the levels of this study, suppresses development of deep surface cracks in the presence of intermediate residual level of Sn, but not with high residual level of Sn.
- Surface crack depth increases when tensile strain rate is lowered to 0.005 s^{-1} .
- Surface crack depth decreases dramatically at the higher test temperatures 1200 and 1300°C.

5.2.2 Low-Carbon Steels

- Copper addition at the level of this study in the absence of Ni and Sn does not result in development of deep surface cracks.

- Copper addition at the level of this study combined with intermediate residual level of Sn results in development of deep surface cracks at 1000 and 1100°C, and not at 1200 and 1300°C, with or without the addition of Ni.
- Surface crack depth decreases dramatically at the higher test temperatures 1200 and 1300°C.
- In general, the results provide, within the scope of the experimental program, guideline data on acceptable residual levels and reheat temperatures that would not result in deep surface crack formation during reheating and hot-rolling of the selected grades of steel.

5.3 SCALE FORMATION AND ADHERENCE

5.3.1 Scale Growth

- Additions of residual elements Cu, Sn, Ni and P at the levels of this study in both medium- and low-carbon steels have little or no effect on oxide growth rates after one hour of oxidation. Oxidation rate increases with increasing oxidation temperature. Oxidation rate also consistently increases when moisture (steam) is introduced to the oxidation furnace atmosphere.
- The oxide scale formed on both medium- and low-carbon steels mainly consists of an inner wustite layer (FeO), an intermediate magnetite layer (Fe₃O₄), and in some cases a thin outer layer of hematite (Fe₂O₃).
- Residual element additions result in additional phases such as metallic compounds and iron silicates embedded in the inner wustite layer at and near the steel/scale interface. These effects are more pronounced in the medium-carbon steels which have higher residual levels. The presence of Ni in medium-carbon steels results in development of a more irregular steel/scale interface.

5.3.2 Scale Adherence

- Scale adherence increases with increasing oxidation temperature, particularly in the medium-carbon steels.
- Scale adherence increases dramatically with addition of moisture to the oxidation atmosphere, particularly in the medium-carbon steels at the higher temperatures 1100 and 1200°C.
- Scale adherence increases in medium-carbon steels containing residual Cu and Ni, particularly at the higher temperatures 1100 and 1200°C and when oxidized in moist atmosphere.
- Scale adherence does not consistently increase in medium- and low-carbon steels containing the higher level of Si.
- Scale adherence in low-carbon steels where the residual levels were lower is minimal in comparison

to that of medium-carbon steels.

- The results provide guideline data on steel composition and oxidation temperature and atmosphere conditions required to minimize scale adherence resulting from a steel reheating process.

5.4 MECHANICAL PROPERTIES

- Addition of residuals in both medium- and low-carbon steels affect microstructure by decreasing ferrite grain size by up to 29%.
- Increasing residual content increases tensile properties (YS and UTS) in both medium- and low-carbon steels. Strength increases are effected primarily by ferrite grain refinement, and secondarily by solid solution hardening. Strengths are decreased slightly by the recovery softening effect of the step-cooling heat-treatment.
- Addition of residuals at the levels of this study in both medium- and low-carbon steels in the hot-rolled condition have little effect on Charpy impact toughness. Higher Mn and Si levels in the hot-rolled plate-composition low-carbon steel significantly increase impact toughness by lowering the transition temperature 80°C. After step-cooling heat-treatment to maximize grain boundary segregation, the 40J transition temperatures are increased by up to 28°C in the steels with the higher Mn and Si contents, and are changed very little in the steels with low Mn and Si levels. These results indicate that grain boundary segregation requires the presence of alloy elements such as Mn and Si.
- AES analysis of in-situ fractured samples revealed Sn enrichment (segregation) on intergranular boundary facets in the embrittlement-sensitive medium- and low-carbon steels after step-cooling heat-treatment.
- The results indicate how the microstructure (ferrite grain size, pearlite volume fraction) developed in reheating and hot-rolling processing of the steel can affect its mechanical properties. Embrittlement effects of residual segregation in the as-hot-rolled steels are small and should not cause serious problems in practice.

REFERENCES

1. L. F. Verdeja, J. P. Sancho and J. I. Verdeja; "Iron and Steel Making in the Third Millennium", CIM Bulletin, Vol. 95, July 2002, pp. 88-95.
2. W. E. Dennis; "The Resurgence of Steel", ASTM Standardization News, February 1995, pp. 36-41.
3. H. A. Faure; "Development, State of the Art and Future Aspects of Steelmaking", La Revue de Metallurgie – CIT, Vol. 90, November 1993, p. 1440.
4. S. J. Home; "Design for Recycling – An Essential Component of Any Automobile", presented at The Conference of Metallurgists (CIM), Toronto, Ontario, August 27, 2001.
5. E. Worrell, N. Martin and L. Price; "Energy Efficiency Opportunities in Electric Arc Steelmaking", Iron & Steelmaker, Vol. 26, No. 1 (January 1999), pp. 25-32.
6. M. J. Thomson, E. J. Evenson, M. J. Kempe and H. D. Goodfellow; "Control of Greenhouse Gas Emissions from Electric Arc Furnace Steelmaking: Evaluation Methodology from Case Studies", Ironmaking & Steelmaking, Vol. 27, No. 4 (2000), pp. 273-279.
7. S. Friedman; "Climate Change and the Iron and Steel Industry", Iron & Steelmaker, Vol. 26, No.1 (January 1999), pp. 17-23.
8. J. Stubbles; "History of Minimills in Steelmaking", CIM Bulletin, Vol. 95, January 2002, pp. 82-88.

Fig. 1. Effect of deformation temperature on hot ductility (RA%) and maximum load of the base medium carbon steel, M1.

Fig. 2. Fractured Gleeble samples of Steel M1.

Fig. 3 is shown in page 46.

Fig. 4. Fracture surface of M1 and EDX analysis of Mn sulphide particle (at arrow) after Gleeble testing at 700°C.

Fig. 5. Effect of deformation temperature on hot ductility (RA%) and maximum load of the base low carbon steel, L1.

Fig. 6. Fractured Gleeble samples of Steel L1.

(a) L1 at 750°C with 81% RA

(b) L1 at 850°C with 56% RA

(c) L1 at 1000°C with 91% RA

Fig. 7. Fracture surfaces of L1 after Gleeble testing at different temperatures.

(a) L1 at 750°C with 81% RA

(b) L1 at 850°C with 56% RA

(c) L1 at 1000°C with 91% RA

Fig. 8. Fracture surfaces of L1 after Gleeble testing at different temperatures.

Fig. 9. L2 WQ (600°C), showing proeutectoid grain-boundary ferrite.

Fig. 10. Average surface crack depth of M-Series alloys after tensile testing to 40% elongation with a strain rate of 5 s^{-1} at 1100°C .

Fig. 11. Depth distribution of surface cracks of M-Series alloys after tensile testing to 40% elongation with a strain rate of 5 s^{-1} at 1100°C .

Fig. 12. SEM photograph showing scale/metal interface properties of M6 alloy subjected to tensile testing with a strain rate of 5 s^{-1} at 1100°C .

Fig. 13. Average surface crack depth of L-Series alloys after tensile testing to 40% elongation with a strain rate of 5 s^{-1} at 1100°C .

Fig. 14. Depth distribution of surface cracks of L-Series alloys after tensile testing to 40% elongation with a strain rate of 5 s^{-1} at 1100°C .

Fig. 15. Weight change curves for the oxidation of medium carbon steel alloys at 1200°C in dry air atmosphere.

Fig. 16. Effect of furnace atmosphere on the total weight change after one hour of oxidation of medium carbon steel alloys at 1200°C.

Fig. 17. Effect of temperature on the total weight change from oxidation of medium carbon steel alloys for one hour in air-H₂O atmosphere.

Fig. 18. SEM images of oxides formed on medium carbon steels M7 and M9 after one hour of oxidation at 1200°C in dry air.

Fig. 19. SEM images of oxides formed on medium carbon steel M9 after one hour of oxidation at 1100°C in air-H₂O atmosphere.

Fig. 20. Effect of furnace atmosphere on the total weight change after one hour of oxidation of low carbon steel alloys at 1200°C.

Fig. 21. Effect of temperature on the total weight change after one hour of oxidation of low carbon steel alloys in air-H₂O atmosphere.

Fig. 22. Effect of furnace atmosphere on the scale adherence of medium carbon alloys oxidized for one hour at 1200°C.

Fig. 23. Effect of oxidation temperature on the scale adherence of medium carbon alloys oxidized for one hour in moist air atmosphere.

Fig. 24. Effect of oxidation temperature on the scale adherence of low carbon steel alloys oxidized for one hour in moist air.

Fig. 25. Effect of furnace atmosphere on the scale adherence of low carbon alloys oxidized for one hour at 1200°C.

Fig. 26. Engineering tensile stress vs strain curve of hot-rolled L1 and L12 steel samples.

Fig. 27. Effect of residuals on strengths of med.-C steels in hot-rolled condition.

Fig. 28. Effect of step-cooling treatment on yield strengths of medium carbon steels.

Fig. 29. Charpy transition curves of med.-C steels in the hot-rolled condition.

Fig. 30. Charpy transition curves of low-C steels in hot-rolled condition.

Fig. 31. Effect of residuals on Charpy transition curve of M3 steel (HR – hot-rolled; SC – step-cooled)

Fig. 32. Effect of residuals on Charpy transition curve of L13 steel (HR – hot-rolled; SC – step-cooled).

(a) Hot-rolled condition (about 6% intergranular fracture)

(b) Step-cooled condition (about 20% intergranular fracture)

Fig. 33. SEM fractographs of L13 Charpy specimens tested at -196°C .

Fig. 34. SEM photograph of AES L13 (SC) sample A showing spots for Auger analysis, enlarged view (orig. 635x, 200 μm edge-to-edge).

Fig. 35. Typical Auger spectra of L13 (SC) – Sample A, Spot 2 showing an AES spectrum at a segregated grain boundary facet

Fig. 36. Schematic diagram of ductility curve defining the trough area and temperature of $R1 = 60\%$ reduction in area.

Fig. 37. Comparison of ductility curves of the base low- and medium-carbon steels, i.e., L1 and M1 steels.

Fig. 3. Hot ductility curve and fracture surfaces of M1 after Gleeble testing at different temperatures.