Degradation Mode Survey of Titanium - Base Alloys

G.E. Gdowski
Lawrence Livermore National Laboratory
Livermore, California 94550

H.S. Ahluwalia
Science and Engineering Associates, Inc.
Livermore, California 94550

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

59

Table of Contents

Page

1.0	Introduction	
2.0	Physical Metallurgy and Microstructure.....	
2.1	Introduction	
2.2	Phase Diagrams	
2.3	Bulk Microstructure	
3.0	Mechanical and Physical Properties.....	
4.0	Weldability and Weldment Corrosion	
5.0	Corrosive Environment Considerations	
6.0	Oxide Film	
6.1	Film Composition and Structure	
6.2	Pourbaix Diagram.....	
7.0	General Corrosion Resistance	
8.0	Pitting Corrosion	
9.0	Crevice Corrosion.....	
9.1	Temperature	
9.2	Solution Chemistry and pH.....	
9.4	Physical Characteristics of a Susceptible Crevice.....	
9.5	Alloy Composition.....	
9.6	Surface Condition.....	
9.7	Metal Potential	
10.0	Sustained Load Cracking	
11.0	Hydrogen Embrittlement.....	
11.1	Mechanism.....	
11.2	Physical Properties.....	
11.3	Effect of the Surface Layer on Hydrogen Uptake	
11.4	Effect of pH on Hydrogen Uptake	
11.5	Galvanic Coupling.....	
12.0	Stress Corrosion Cracking.....	
13.0	Galvanic Corrosion.....	
14.0	Radiation Environment	
15.0	Additional Corrosion Studies of Titanium Alloys	
16.0	Summary.....	
17.0	References.....	

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

1.0. Introduction

The Yucca Mountain Site Characterization Project (YMP) has the task of selecting materials from which to fabricate high-level nuclear waste containers for the potential repository at Yucca Mountain, Nevada [MCC95a]. Because of their very good corrosion resistance in aqueous environments titanium alloys are considered for container materials [MCC95b]. Consideration of titanium alloys is understandable since about one-third of all titanium produced is used in applications where corrosion resistance is of primary importance [MIN78]. Consequently, there is considerable amount of data which demonstrates that titanium alloys in general, but particularly the commercial purity and dilute α grades, are highly corrosion resistant [SCH86, FEI70, COV77].

The highest resistance to corrosion and hydrogen embrittlement effects is found in commercial purity (C.P.), dilute α -grades of Ti (titanium content ≥ 98.9 wt.%), and other titanium alloys with Pd additions. Titanium alloys commonly used in corrosion resistant equipment or proposed for this purpose are shown in Table 1.1. These alloys are different grades of C.P. titanium (Ti Gr 1-3), α -Ti with small Pd content (Ti Gr 7, 11, and 16), the Ti-0.3%Mo-0.8%Ni alloy (Ti Gr 12), and other higher alloyed Ti alloys with Pd additions. (Note: Ti Gr 11 has the same Pd content as Ti Gr 7, but it has a lower impurity content and hence a higher cost. Ti Gr 7 is more commonly used than Ti Gr 11.)

Both the titanium-palladium alloys and the Ti Gr 12 alloy are used in applications requiring better corrosion resistance than that of the C.P. titanium. Titanium-palladium alloys are used where the corrosive media is mildly reducing or fluctuates between oxidizing and reducing. The lower Pd addition alloy (Ti Gr 16) is not as corrosion resistant as the high Pd addition alloy (Ti Gr 7), however, Ti Gr 16 has significantly better corrosion resistance than C.P. titanium and is less costly than Ti Gr 7 [SCH93]. It should be noted that Ti Gr 16 is a new alloy and therefore limited amounts of information are available. Palladium additions are within the solid solution solubility limits in α -Ti. The characteristics of good fabricability, weldability, and strength level are similar to those of corresponding unalloyed titanium grades [LAM90]. Ti Gr 12 has better corrosion resistance and higher strength than those of C.P. titanium. However, the corrosion resistance is generally not as good as Ti Gr 7. This report will

discuss the corrosion characteristics of Ti Gr 2, 7, 12, and 16. (The more highly alloyed Ti Gr 5/Pd and Gr 18 which were developed by adding a small Pd content to higher strength Ti alloys in order to give them better corrosion resistance will not be considered in this report.)

Table 1.1. Composition (wt.%) of corrosion resistant titanium alloys [SAE93].

UNS	ASTM	C	Fe	H	N	O	Ti	Pd	Ni	Mo	Other
R50250	TiGr1	0.10	0.20	0.015	0.03	0.18	rem				
R50400	TiGr2	0.10	0.30	0.015	0.03	0.25	rem				
R50550	TiGr3	0.10	0.30	0.015	0.05	0.35	rem				
None to date	TiGr5 /Pd							0.05			Al: 6 V: 4
R52250	TiGr11	0.10	0.20	0.015	0.03	0.18	rem	0.12-0.25			
R52400	TiGr7	0.10	0.30	0.015	0.03	0.25	rem	0.12-0.25			
R53400	TiGr12	0.08	0.30	0.015	0.03	0.25	rem		0.6-0.9	0.2-0.4	
None to date	TiGr16						rem	0.05			Ru: 0.2
None to date	TiGr18						rem	0.05			Al: 3 V: 2.5
R54625		0.08	1.3-2.0	0.012-5	0.04	0.15-0.20	rem	0.04-0.08			Al: 5.5-6.5 Si: 0.07-0.13 Other residual elements: 0.30 max

2.0 Physical Metallurgy and Microstructure

2.1 Introduction

Titanium is an allotropic element; that is, it has more than one crystallographic form. Above 883°C it has a body-centered cubic (bcc) crystal structure, which is called the beta (β) phase. Below 883°C, it transforms to a hexagonal closed-packed (hcp) structure, which is called the alpha (α) phase.

Alloying elements can either stabilize the β or α phase microstructure. Some α -phase stabilizers, which increase the temperature to which the α phase is stable, are Al, Ga, Ge, Sn, C, O, and N. Some β -phase stabilizers, which stabilize the β -phase to lower temperatures, are Fe, Mn, Cr, Mo, and V. Substitutional elements generally tend to be β -phase stabilizing. The β transus temperature is the lowest equilibrium temperature at which the α or $\alpha + \beta$ structure transforms to all β microstructure.

Two groups of elements stabilize the β phase structure. The group of elements that are miscible in the β phase, including Mo, V, Ta, and Nb, are called the β isomorphous group. Elements in the other group promote the eutectoid reaction at temperatures as much as 333°C below the β -transus temperature of unalloyed titanium. The eutectoid forming elements include Mn, Fe, Cr, Co, Ni, Cu, and Si.

2.2 Phase Diagrams

Three titanium alloys systems are considered: 1) commercially pure titanium (Ti Gr 2), 2) titanium with less than or equal to 0.2% Pd (Ti Gr 7 and 16), and 3) a dilute titanium alloy (Ti Gr 12). All three systems are α or near- α Ti alloys.

Ti Gr 7 and 16 are titanium alloys with a very small additions of palladium, 0.2 and 0.05 wt.% respectively. The phase diagram for the binary system Pd-Ti is shown in Fig. 2.1 [MAS90]. The maximum solubility of Pd in α titanium is about 2 wt.% at 595°C. As the temperature decreases from 595°C the solubility decreases. At 400°C the Pd solubility in α titanium is about 1 wt.%. At higher

Pd concentrations there is a two-phase region of α -Ti(Pd) and an intermetallic phase. The intermetallic phase is either Ti_4Pd or Ti_2Pd ; the existence of the latter phase is uncertain. The nominal Pd concentrations of Ti Gr 7 and 16 are both well below the solubility limits at 400°C. The higher Pd content alloy (Ti Gr 7) was developed such that all the Pd remains in solid solution.

Ti Gr 12 has small additions of Mo (0.3 wt.%) and Ni (0.8 wt.%). Nickel solubility in α titanium is small; less than 0.05 wt.% at 300°C. At temperatures below 765°C and nickel concentrations greater than 0.1 wt.%, an intermetallic phase Ti_2Ni forms (Fig. 2.2) [MAS90]. The solubility of molybdenum in α titanium is very small (below 0.1wt.%) at temperatures below 400°C. At higher molybdenum concentrations there is a mixture of α -Ti and $\beta(\text{Mo,Ti})$ (Fig. 2.3) [MAS90]. The Ti Gr 12 microstructure is a mixture of α -Ti, Ti_2Ni intermetallic, and β -Ti.

2.3 Bulk Microstructure

The bulk microstructure of α -Ti alloys is dependent on heat treatment and working of the material [BOY85]. The α alloys (Ti Gr 2, 7, and 16) consist of equiaxed α grains after annealing cold-worked alloys above the recrystallization temperature range. The microstructure is hexagonal closed packed (hcp) below 890°C and body centered cubic (bcc) above about 913°C. The transition temperature is influenced by amounts and kinds of impurity elements present. Elongated α grains result from unidirectional working of the metal and are commonly found in longitudinal sections of rolled or extruded alloys.

Generally, two types of α , primary α and secondary α or transformed β , are present in titanium alloys [BOY85]. Primary α is that α which persists through heat treatment and cold working. Secondary α is that α produced by transformation of β with cooling. This can result from cooling from above the β transus or aging of nonequilibrium β . The α in these areas has a unique appearance and may be acicular or lamellar, platelike, serrated, or Widmanstätten [BOY85].

The microstructure of titanium alloys is influenced by heat treatment and processing history [BOY85]. With increasing cooling rate, the spacing of the lamellar α (or martensite, depending on the alloy and cooling rate) becomes finer. With increasing forging or heat-treatment temperature, the amount of transformed β increases until the forging or heat-treatment temperature is above the β transus, at which point the structure is 100% transformed β . Sufficient working of the cast Widmanstatten structure at a temperature below the β transus causes recrystallization of the lamellar structure to a more equiaxed structure. Sufficient working and proper heat treatment can produce a completely equiaxed crystal structure.

Acicular or lamellar α is the most common transformation product formed from β during cooling [BOY85]. It results from nucleation and growth occurring on specific crystallographic planes of the prior β matrix. Precipitation normally occurs on multiple variants or orientations of this family of habit planes. A "colony" is a packet or cluster of acicular α grains aligned in the same orientation. When correlating this type of microstructure with properties such as fatigue or fracture toughness, colony size is an important microstructural feature. The multiple orientations of α have a basket weave appearance characteristic of a Widmanstatten structure. A singular orientation results from lamellar α forming from small β grains.

Other α microstructures can occur, depending on nucleation conditions [BOY85]. Long grains of α that are produced along preferred planes in the β matrix take on a platelike appearance. Grains of irregular size and with jagged boundaries, called "serrated α " are also possible.

The microstructures of Ti Gr 7 and 16 are the same as for equivalent grades of unalloyed titanium, since only small α soluble amounts of palladium are added to make these Ti-Pd alloys. Titanium-palladium intermetallic compounds capable of being formed in this system have not been reported to occur in Ti Gr 7 and 16 with normal heat treatments. Transformation temperatures are similarly expected to remain unchanged.

The microstructure of Ti Gr 12 consists of equiaxed α grains with 10 -15% (by volume) of β phase located primarily along grain boundaries and at grain

boundary triple points. The intermetallic compound Ti_2Ni is observed at α / β interfaces and within the β phase. The Ti_2Ni phase forms through the eutectoid reaction

Acicular α microstructures are found primarily in welds or heat affected zone [MOL83].

Unless heat treatments are performed in an inert atmosphere, oxygen and nitrogen will react with titanium and form a hard brittle layer referred to as an " α case" [BOY85]. (Oxygen and nitrogen are both α stabilizers.) This " α case" must be removed before the part is put into service.

3.0 Mechanical and Physical Properties

Some of the mechanical properties of some commercially available titanium alloys at room temperature and 300°C are shown in Table 3.1. There are significant increases in yield strength and ultimate tensile strength as the impurity content, particularly that of oxygen and iron, increases. Similarly, intentional alloying additions produce significant strength increases. The small alloying additions in Ti Gr 12 result in a significant strengthening of the titanium by introducing a small amount of β phase to the microstructure, and by solid solution strengthening. However, the small Pd additions in Ti Gr 7 and 16 do not significantly change the mechanical properties in comparison to Ti Gr 2, an alloy with a similar amount of impurities.

Table 3.1. Tensile properties of wrought titanium alloys at room temperature and 300°C. Properties are for materials in the annealed condition. Values are given as range with the minimum value or as an average or typical value [LAM94, DON88].

Alloy	Room Temperature			
	Ultimate tensile strength MPa (ksi)	0.2% yield strength MPa (ksi)	Elongation %	Reduction in area %
Gr 1	240-331 (35-48)	170-241 (25-35)	30	55
Gr 2	340-434 (50-63)	280-345 (40-50)	28	50
Gr 3	450-517 (65-75)	380-448 (55-65)	25	45
Gr 4	550-662 (80-96)	480-586 (70-85)	20	40
Gr 7	340-434 (50-63)	280-345 (40-50)	28	50
Gr 12	480-517 (70-75)	380-448 (55-65)	25	42

Alloy	300°C			
	Ultimate tensile strength MPa (ksi)	0.2% yield strength MPa (ksi)	Elongation %	Reduction in area %
Gr 1	152 (22)	97 (14)	32	80
Gr 2	193 (28)	117 (17)	35	75
Gr 3	234 (34)	138 (20)	34	75
Gr 4	310 (45)	172 (25)	25	70
Gr 7	186 (27)	110 (16)	37	75
Gr 12	324 (47)	207 (30)	32	...

One disadvantage of titanium and its alloys is that their strength decreases rather rapidly with increasing temperature (Fig. 3.1). This is due to the strong temperature dependence of interstitial solute strengthening mechanisms. The yield and ultimate tensile strength values for Ti Gr 12 always remain higher relative to unalloyed Ti Gr 2 and Ti-Pd (Ti Gr 7).

Allowable stress values from the ASME pressure vessel code for titanium alloys also decrease as a function of increasing temperature (Table 3.2) [COV89]. The allowable stress for Ti Gr 12 are higher at all temperatures than are those for Ti Gr 2 (unalloyed Ti) and Ti Gr 7 (Ti-0.2%Pd). At 260°C (500°F), the design stress for Ti Gr 12 is 70% greater than that of either Ti Gr 2 or 7.

Table 3.2. Design stresses (ksi) for titanium plate^{a,b}.

For metal temperatures not exceeding (°C)	Gr 2 (Ti-50A)	Gr 3	Gr 7 (Ti-0.2Pd)	Gr 12 (Ti-0.3Mo- 0.8Ni)
38	12.5	16.3	12.5	17.5
93	10.9		10.9	16.4
149	9.0	11.7	9.0	14.2
204	7.7		7.7	12.5
260	6.6		6.6	11.4
316	5.7	6.0	5.7	

a - ASME Section VIII, Division 1 - Pressure Vessels

b - Design stress for Ti Gr 16 should be similar to Ti Gr 2 and 7, since this property is a function of impurity content.

The physical properties of titanium and its alloys must be considered when designing or fabricating equipment from these materials (Table 3.3) [SCH86]. Titanium alloys have densities slightly over half those of iron or copper-based alloys. The modulus of elasticity of titanium is also about half that of steel. Specific heat and thermal conductivity are similar to those of stainless steel.

Titanium has a relatively high electrical resistivity and low thermal expansion coefficient.

Table 3.3. Physical properties of some titanium alloys [SCH86].

Property	Titanium Alloy			
	Gr 1	Gr 2	Gr 3	Gr 12
Density (g/cm ³)	4.54	4.54	4.54	4.55
Melting point (°C)	1660	1678	1660	---
Beta transus (°C)	888	913	921	885
Specific heat (joules/g/°C)	0.51	0.52	0.52	0.54
Thermal Conductivity (W/m •°K)	15.6	16.4	16.4	19.0
Coefficient of expansion (10 ⁻⁶ /°C)	9.0	9.0	9.0	9.0
Electrical resistivity (μohm•cm)	56	56	57	52
Modulus of elasticity (10 ³ MPa)	103	103	103	103
Poisson ratio	0.34	0.34	0.34	0.34

Note: Ti Gr 7 and 16 should have similar properties to Ti Gr 2, since these properties are primarily dependent on impurity content. The exception may be electrical resistivity.

4.0 Weldability and Weldment Corrosion

Titanium alloys are readily weldable with processes that exclude interstitial contaminants such as C, O₂, H₂, and N₂ from the fusion and heat-affected zones of the weldment. These processes include gas-tungsten-arc welding (GTAW), gas-metal-arc welding (GMAW), resistance, plasma, inertia (friction), pressure, and electron beam welding methods [SCH86].

The use of inert-gas shielding during welding is essential due to the high affinity of titanium for oxygen, nitrogen, carbon, and hydrogen. These elements dissolve interstitially and can result in severe embrittlement when present in relatively small quantities. Therefore, additional inert gas shielding must be provided during welding to protect those parts close to the molten pool. Good techniques for inert gas shielding of welds, which involve use of trailing shields

as well as shielding of the root surfaces of the weldment, have been developed. Use of these techniques, together with careful procedures to exclude all moisture, dirt and other foreign matter from the weld area, assure good welds [COV89].

Proper attention to the details described above results in weld properties equivalent to those of the base metal. Contamination of welds results in loss of ductility and toughness, as well as degraded corrosion resistance.

Weldments of Ti Gr 1-4, Gr 7, and Gr 12 generally exhibit corrosion resistance similar to that of their unwelded, wrought counterparts. Therefore, titanium alloy weldments and associated heat-affected zones generally do not experience corrosion limitations in welded components when normal passive conditions prevail for the base metal. However, under marginal or active conditions (for corrosion rates ≥ 0.10 mm/yr or 4 mils/yr) weldments may experience accelerated corrosion attack relative to the base metal, depending on alloy composition. The increasing impurity (iron, sulfur, oxygen) content associated with the coarse, transformed- β microstructure of weldments appears to be a factor.

5.0 Corrosive Environment Considerations

This report is concerned with the aqueous phase corrosion of the titanium alloys. This includes corrosion that can occur in bulk aqueous phases and also corrosion that occurs in thin water films present on surfaces in high relative humidities. The potential repository at Yucca Mountain is in the unsaturated zone, that is, it is located above the water table, therefore, water contact will be at ambient pressure and at or below the ambient boiling temperature. Crevice and hygroscopic salts will raise the temperatures at which water is in contact with the container to temperatures higher than the ambient boiling temperature. The water that does come in contact with the waste containers is expected to have a low ionic content (sulfate, chloride, carbonate), a near neutral pH, and to be oxidizing. However, bounding aqueous solution compositions are also considered for credible water contact scenarios. These are: concentrated solutions, because of evaporation or boiling; low pH solutions because of

microbial activity; and high pH solutions because of cementitious material in the repository. Various thermal loading scenarios have been considered for the repository with maximum container temperatures not expected to exceed 250-300°C. Since the repository site will be at atmospheric pressure aqueous corrosion phenomena will be limited to maximum temperatures near the ambient boiling temperature. The possibility of galvanic coupling of the titanium alloys to other materials is also considered because of the potential use of multiple metallic barriers.

6.0 Oxide Film

6.1 Film Composition and Structure

The excellent corrosion resistance of titanium alloys results from the formation of a very stable, continuous, highly adherent, and protective oxide film. Because titanium metal itself is highly reactive and has an extremely high affinity for oxygen, these beneficial surface oxide films form spontaneously and instantly when fresh metal is exposed to air and/or moisture. In fact, a damaged oxide film can generally reheal itself instantaneously if at least a few parts per million of oxygen or water (moisture) are present in the environment. However, anhydrous conditions in the absence of a source of oxygen may result in titanium corrosion, because the protective film may not be regenerated if damaged.

The nature, composition, and thickness of the protective surface oxides that form on titanium alloys depends on environmental conditions, and this in turn significantly affects the material's corrosion resistance. According to Tomashov et al. [TOM82] film composition varies from TiO_2 at the surface, through Ti_2O_3 below the surface, to TiO at the metal interface. High temperature oxidation tends to promote the formation of the chemically-resistant, highly-crystalline form of TiO_2 , known as "rutile". Lower temperature oxidation often result in formation of the anatase form of TiO_2 , or a mixture of rutile and anatase. Although these naturally-formed films are typically less than 10 nm [AND64] thick and are invisible to the naked eye, they are extremely resistant to

degradation. However, strongly oxidizing solutions, such as immersion in concentrated HNO_3 , will accelerate their growth.

Oxides formed on Ti alloys in aqueous environments at elevated temperatures (95°C) are amorphous [MAT84]. The oxide consists of an outer layer of TiO_2 and a few atomic layers of suboxide (Ti_2O_3) next to the oxide/metal interface. The structure of the oxide is not significantly influenced by the oxygen content (saturated or deoxygenated) or NaCl content (0 or 1 wt.%). In neutral water, the outer oxide layer is anhydrous, that is, TiO_2 . This is thought to be significant since hydrated titanium oxide is slightly soluble in acid solutions, whereas anhydrous oxide is not. It is concluded that the anhydrous oxide is more corrosion-resistant.

In water-saturated bentonite at 95°C , the constituents of montmorillonite (the main component of bentonite) are embedded within the oxide layer. X-ray photoelectron (XPS) analysis indicates that the simple oxides of the constituent species (Si^{4+} , Al^{3+} , and Mg^{2+}) are present in the oxide. These species appear to be primarily in the outer layers of the oxide and their concentrations decrease as the metal oxide layer is approached. No difference between the oxide structure formed on Ti and Ti-0.2%Pd could be detected.

In contrast to their behavior in neutral aqueous solutions, the oxide layer composition is affected by minor alloying elements when the material is immersed in acid solutions. For Ti-0.2%Pd, there is an enrichment of the more noble Pd metal in the oxide layer caused by dissolution of titanium atoms. The effect of the enrichment in Pd is to increase the ability of the alloy to repassivate. A similar effect has been suggested for titanium alloyed with small amounts of nickel. However the role nickel in enhancing the corrosion resistance of Ti-0.8%Ni-0.3%Mo (Ti Gr 12) is the subject of some debate. It is agreed that nickel is involved in passivation of the alloy, and that the nickel is somehow present in the passive film. Two mechanisms have been proposed. In dilute Ti-Ni alloys, where nickel is present as Ti_2Ni , one mechanism is that the cathodic hydrogen evolution reaction proceeds on Ti_2Ni particles at the surface [TOM82]. The other mechanism suggests that nickel dissolves from the Ti_2Ni particles and is subsequently redeposited as metallic nickel on the titanium surface [SED72]. It has been suggested that Ni atoms are stabilized in the passive film due to a

strongly-bound surface complex involving coordination of the Ni atoms by surrounding titanium oxide species. X-ray photoelectron spectroscopy of surfaces of dilute Ti-Ni alloys, after corrosion in acid sulphate solutions, indicate that the oxide film is enriched in nickel, which is in the zero oxidation state [PET80]. It has also been suggested that the passivation of Ti Gr 12 during crevice corrosion is not simply due to enhancement of the hydrogen reduction reaction, but rather that nucleation and growth of a protective surface layer that incorporates nickel as Ni atoms [MCK84].

6.2 Pourbaix Diagram

The Pourbaix (potential-pH) diagram is useful in understanding the corrosion behavior of titanium by recognizing the conditions under which the oxide film is thermodynamically stable. Lee [LEE81] has constructed potential - pH diagrams for titanium in water at temperatures from 25 to 300°C. The Pourbaix diagrams for the Ti-H₂O system at 25, 150, and 300°C are shown in Fig. 6.1. These diagrams show the wide regime over which the passive TiO₂ film is predicted to be stable, based on thermodynamic considerations. Oxide stability over the full pH scale is indicated over a wide range of highly oxidizing to mildly reducing potentials, whereas oxide film breakdown and the resultant corrosion of titanium occurs under reducing acidic conditions. At temperatures higher than 150°C, strong alkaline solutions tend to dissolve TiO₂, forming the acid oxy-anion of titanium (HTiO₃⁻). The stable domain of HTiO₃⁻ is expanded as the temperature increases. Thus, a region of dissolution of titanium in alkaline solutions is expected at higher temperatures. The standard electrode potential for the Ti-Ti⁺⁺ reaction is -1.628 V at 25°C and becomes more negative with increasing temperature to a value of -1.665 at 300°C. It was observed that the stability of titanium and its oxides in acidic solution increases with increasing temperature, but their stability is decreased in alkaline solutions at higher temperatures. According to the Pourbaix diagram, neutral or slightly alkaline water at higher temperatures should not affect the TiO₂ film.

7.0 General Corrosion Resistance

In 1978 it was estimated that about one-third of all titanium produced is used in applications where corrosion resistance is of primary importance [MIN78]. Consequently there is data which demonstrates that titanium alloys in general, but particularly the commercial purity and dilute α Ti grades, are highly corrosion resistant [FEI70, COV77].

Titanium retains its corrosion resistance to 315°C or more. At higher temperatures, the film is destroyed because oxygen diffuses into the base metal, greatly lowering corrosion resistance. Although the TiO_2 film is highly corrosion resistant, it will be attacked by a few substances, including hot concentrated HCl, H_2SO_4 , NaOH, and HF.

General corrosion rates that have been reported in near-neutral aqueous solutions indicate that very low corrosion rates would be expected after the initial formation of the protective oxide film. At 95°C, the oxide layer is 60Å after 10 days, however, based on tests of 6 month duration, the long-term growth is expected to follow a logarithmic law, which is given by [MAT85]:

$$y = 8.7 + 3.65 \ln(t)$$

where t is time in seconds, and y is the oxide thickness in Å. Oxygen (saturated and deoxygenated) and NaCl (0 or 1%) concentration did not significantly affect the growth rate.

In water-saturated bentonite at 80°C the film growth rate is logarithmic and given by [MAT85]:

$$y = 5.5 \ln(t).$$

The relationship is based on exposures from 4 months to 2 years. However, longer exposure periods (years) indicate that the rate increases with time; this increase is thought to be due to the crystallization of the initially amorphous oxide layer, which allows easier ionic transport along grain boundaries

[MAT85]. There is no significant difference in the corrosion rates for Ti and Ti-0.2%Pd.

The environment in which the oxide layer is formed significantly affects its corrosion resistance [BRA80]. Oxide layers formed in different environments at 25°C were subsequently immersed in 6N H₂SO₄. The potential of the specimens was monitored as a function of time. For all specimens, the potential decreased and eventually reached a stable value at about -0.65 V(SCE). This was thought to be due to a reduction of the oxide layer. Those specimens with oxide layers formed with both oxygen and water present show the most resistance to reduction processes. Oxide layers formed in dry air have a factor of 3 or 4 less resistance.

A more corrosion-resistant oxide layer was found to be formed by thermal oxidation than by either anodization or pickling [SCH81]. Better corrosion resistance was found for thermally oxidized (677°C, 1 minute) specimens in solutions of less than 0.8 % HCl for 100 hr exposures. For 300 hr exposures thermal oxide stability is seen only for solution up to 0.5% HCl. Thermal oxide films are also very tenacious in simple acid pickling solutions, whereas anodized films can rapidly be removed by the acid pickle. In general, thermal oxide films must be sandblasted or processed in a caustic descaling bath to effect removal.

An enhanced short term benefit for thermal oxidation of Ti Gr 7 and 12 was also found for resistance to corrosion in the 0.8 HCl solutions [SCH81]. The benefit did not extend to longer times (100 hr exposures). However, the corrosion resistance of Ti Gr 7 and 12 was still better than that of Ti Gr 2 with or without the thermal oxide.

The thermal oxide layer on pure titanium enhanced its resistance to crevice corrosion and hydrogen embrittlement [SCH81]. Thermal oxidation can offer significant improvement in crevice corrosion resistance of pure titanium in chlorides, particularly in the unstrained condition. The extent of the extra crevice corrosion protection is somewhat reduced when the thermally oxidized titanium has been plastically strained. Thermal oxidation (627°C, 1 min) can reduce the hydrogen uptake efficiency by a factor of two during cathodic

charging at 1.0 mA/cm^2 in comparison to pickled specimens. Longer oxidation times result in even greater reduction of hydrogen uptake. Thermal oxidation can increase corrosion resistance if titanium is galvanically coupled to a less noble material.

8.0 Pitting Corrosion

Titanium has been shown to be susceptible to pitting corrosion caused by iron particles that have been embedded in and penetrated the passive film [DON88]. The difference in corrosion potential between low-carbon steel and unalloyed titanium is nearly 0.5V in saturated brine at temperatures near the boiling point. This difference is sufficient to establish an electrochemical cell in which the iron is consumed at the anode. Before the iron is completely consumed, however, a pit begins to grow in the titanium. Once the pit becomes established, acid conditions develop in it. These conditions prevent the passive film from reforming, and corrosion continues until the titanium is perforated [DON88].

Care must be exercised during fabrication and installation of titanium equipment to ensure that it is not contaminated with embedded iron particles. Also as a final operation step, anodizing the titanium helps remove iron particles and enhances corrosion resistance of the passive film [DON88].

9.0 Crevice Corrosion

Titanium alloys are susceptible to crevice corrosion within tight physical crevices, when exposed to hot chloride, bromide, iodide, fluoride, or sulfate-containing aqueous solutions [SCH92a,b]. Susceptible crevices can be formed from adhering scales that promote acidic reducing conditions (e.g. siliceous deposits) and metal-to-metal joints (incomplete fusion of weldments). Mechanical damage to metal surfaces, such as by abrasion and scratching can cause the formation of metal laps or smears under which crevice corrosion can initiate.

Titanium alloy crevice attack typically manifests itself as irregular shaped, open-mouth pits with high aspect ratios. A voluminous, adhering, tenacious, and gray or off-white colored titanium dioxide (TiO_2) corrosion product usually fills and caps these pits. The attack in the pit is either uniform and/or intergranular, and a rim layer of acicular titanium hydride precipitates along attacked surfaces. The penetration depth of the hydride precipitates depends on temperature; at low temperatures (70-130°C) significant hydride layers may form, and at high temperatures (> 130°C) only thin hydride layers are present because of significant hydrogen diffusion and penetration into the metal.

Crevice corrosion may also take the form of circular pits with tiny rounded caps or minimal apparent TiO_2 corrosion product scale formation. This less common form of attack can result when a titanium surface has been gouged, scratched, smeared, or embedded with iron, carbon steel, or low alloy steel, and exposed to a hot concentrated chloride brine (See Section 8.0). Small circular pits may also form in cases where high local acidity may develop within creviced sites or under deposits. This can occur under deposits and in concentrated solutions of hydrolyzable salts (i.e. MgCl_2 , CaCl_2 , AlCl_3 , ZnCl_2 , CaBr_2) at higher temperatures.

The mechanism for crevice corrosion of titanium alloys is similar to that of stainless steels [OLD78]. Within the crevices oxidizing species (e.g. oxygen) are consumed faster than diffusion from the outside bulk solution can replenish them. As a result, metal potentials within crevices become active (negative) relative to the exposed metal surfaces, creating an electrochemical cell in which creviced surfaces become anodic and corrode.

Chlorides diffuse into the crevice and concentrate to maintain mass balance and neutrality with the increasing concentration of dissolved tri- and tetra-valent titanium ions as crevice corrosion proceeds. The titanium chlorides and oxy-chlorides formed are unstable and readily hydrolyze to form titanium oxide corrosion products and more acid; this allows the corrosion process to proceed autocatalytically within the crevice. Studies have determined that pH values as low as 0 to 1 may develop within active crevices [GRI68, MCK84]. The hydrogen produced as a cathodic by-product either recombines to form

hydrogen gas molecules, which evolve from crevices, or is absorbed by interior crevice surfaces forming hydride layers.

Initiation and propagation of titanium alloy crevice corrosion is significantly influenced by temperature, solution chemistry / pH, the physical nature of the crevice, titanium alloy composition, metal surface condition, and metal potential. The following sections discuss the effects of each of these factors.

9.1 Temperature

Titanium susceptibility to crevice corrosion generally increases with increasing temperature [GRI68] provided other conditions are favorable for it to occur. Figure 9.1 shows susceptibility of three titanium alloys to crevice corrosion with increasing temperature and decreasing pH in a saturated NaCl solutions [SCH85]. Unalloyed titanium (Ti Gr 2) becomes susceptible at temperatures greater than 70°C at low to moderate pH values. At temperatures greater than 80-85°C it is susceptible to crevice corrosion in near neutral solutions. Ti Gr 12 becomes susceptible above 75°C, however relatively low pH's are required for crevice corrosion initiation. For temperatures below 100°C, pH levels must be below 2.5 in order for crevice corrosion to occur. Ti Gr 7 is the least susceptible to crevice corrosion. The minimum temperature for crevice corrosion susceptibility is similar to Ti Gr 12, however, much lower pH level are necessary to cause crevice corrosion. For temperature below 100°C, pH levels must be less than 1 for crevice corrosion to occur on Ti Gr 7.

9.2 Solution Chemistry / pH

Titanium is known to be susceptible to crevice corrosion in chloride, bromide, iodide, fluoride, and sulfate solutions. All other conditions considered equal, the threshold for crevice corrosion in fluoride-rich solutions occurs at lower temperatures and higher pH than for the chloride, bromide, iodide, and sulfate solutions [SCH92a]. Crevice corrosion threshold levels of chloride concentration are between 100 and 1,000 ppm, depending on temperature, pH, and the cathodic depolarizers present. Pure sulfate solutions tend to be more benign, with crevice attack occurring at higher sulfate concentrations (>1%) and temperatures (>82°C) [SCH87]. In general, crevice attack increases with

increasing halide concentration, although some studies indicate a maximum in susceptibility in the 1 to 2 M halide range.

Non-oxidizing cations that hydrolyze to form HCl at high concentrations and temperatures may aggravate localized attack. Salts of cations such as Mg^{+2} , Ca^{+2} , Zn^{+2} , and Al^{+3} may aggravate crevice corrosion, while salts of cations such as Na^{+} , K^{+} , and NH_4^{+} will not [SMA81]. In addition, these hydrolyzable salt solutions can produce a special form of localized corrosion on titanium alloys that resembles crevice corrosion except that initiation may occur in the absence of normal crevices [SCH87].

Cathodic depolarizers, such as dissolved oxidizing species and H^{+} ions, dramatically stimulate crevice corrosion initiation and propagation. The critical pH value at which crevice attack occurs varies among the commercial titanium alloys. In hot NaCl-based brines, critical pH levels can vary between 0.7 and 10.5 (Table 9.1), with the best resistance to crevice corrosion shown by the Ti-Pd alloys.

Table 9.1. Critical pH values for crevice corrosion of titanium alloys in hot ($\geq 90^{\circ}C$) NaCl brines [SCH92a].

Alloy	Maximum pH at which attack occurs
Ti-6Al-4V	10-10.5
C.P. Titanium / Ti-3Al-2.5V	9.5-10
Ti-0.3 Mo - 0.8 Mo (Ti Gr 12)	2.5
Ti - 6 Al - 2 Sn - 4 Zr - 4 Mo	2
Ti - 3 Al - 8 V - 6 Cr - 4 Zr - 4 Mo	1
Ti - (0.04-0.25)Pd	0.7-0.8

Other cathodic depolarizing species such as dissolved oxygen, Fe^{+3} , Cu^{+2} , Ni^{+2} , and Ti^{+4} (see Table 9.2 for a more complete list) also enhance titanium's susceptibility to crevice corrosion. (Note this is in contrast to general corrosion where these oxidizing species tend to inhibit corrosion.) Oxygen is an effective accelerator of crevice corrosion even at concentrations of the order of

tenths of a ppm. Although oxygen may only carry 15 to 30 percent of the total crevice corrosion current, it is essential for sustained crevice attack [IKE90]. Therefore deaerated solutions, devoid of any oxidizing species, will not cause significant crevice corrosion. A list of oxidizing anionic species which may diffuse into crevices and inhibit attack in halide-containing solutions is contained in Table 9.2.

Table 9.2. Dissolved oxidizing species which may accelerate or inhibit crevice corrosion of titanium in hot halide solutions [SCH92a].

Accelerate Attack	Inhibit Attack
Fe ⁺³ , Cu ⁺² , Ni ⁺² , Ti ⁺⁴ , Ce ⁺⁴ , Sn ⁺⁴ , VO ₂ ⁺ , Te ^{+4,6} , Se ^{+4,6} , Hg ⁺⁴ , Pt ^{+2,4} , Pd ⁺² , Ru ⁺³ , Ir ⁺³ , Rh ⁺³ , Au ⁺³ , O ₂ , Cl ₂	OCl ⁻ , ClO ₃ ⁻ , ClO ₄ ⁻² , NO ₃ ⁻ , Cr ₂ O ₇ ⁻² , MoO ₄ ⁻² , MnO ₄ ⁻² , S ₂ O ₃ ⁻² , VO ₄ ⁻³ , VO ₃ ⁻ , IO ₃ ⁻ , WO ₄ ⁻

9.4 Physical characteristic of a susceptible crevice

Initiation of crevice corrosion on titanium alloys requires tight, deep crevices. Although the required physical dimensions do vary, typical conditions for aggressive attack are a crevice gap (or width) less than 15 μm and a crevice depth greater than 1 cm. Extremely tight (less than 0.5 μm) crevices (usually formed with sealants and gaskets against metal surfaces) result in greater susceptibility to attack under less aggressive pH/temperature conditions.

Titanium metal-to-metal crevices are generally much less susceptible to attack than gasket-to-metal crevices due to their inherently larger crevice gaps (typically greater than 10 μm). Crevices created between two dissimilar titanium alloys have the crevice corrosion resistance of the more noble alloy because of the galvanically induced anodic protection. In addition, crevices formed between titanium and a number of dissimilar metals may also resist crevice corrosion while for other metals no such protection results (Table 9.3).

Table 9.3. Influence of dissimilar metal crevice members on the crevice corrosion resistance of CP titanium in hot chloride brines [SCH92a].

Inhibit attack	No inhibition
Precious metals (Pt, Pd, Ru, Ir, Rh)	Aluminum alloys
Copper alloys (brass and bronzes)	Zinc
Cu-Ni alloys	Silver
Ni alloys (Monel, 625, C-276)	Niobium
Ni-stainless steels (304, 316)	Molybdenum
Magnesium	Tin
Gold*	Lead

* not effective in hot Cl₂ saturated brines

Severe crevice corrosion may also occur under adherent deposits or scales on titanium metal surfaces. Chloride, sulfate, and siliceous scales can support acidic-reducing conditions (favorable for crevice corrosion) within deposit-metal scales. In contrast, alkaline salt deposits such as carbonates will not support crevice attack. Scales containing significant amounts of oxidizing compounds, such as iron oxides, also inhibit crevice corrosion by passivating creviced metal surfaces.

9.5 Alloy Composition

Titanium alloys that are resistant to corrosion in hot reducing acids are also resistant to crevice corrosion attack. Alloying additions (≥ 0.04 wt.%) of platinum-group metal (Pt, Pd, Ru, and Ir) to practically any titanium alloy significantly enhance crevice corrosion resistance [SCH92a]. Alloys with Pd additions include titanium grades 7, 11, 16, and 18. Nickel additions greater than 0.5 wt.% (as in Ti Gr 12) also increase titanium's crevice corrosion resistance to higher temperatures and lower pHs, relative to unalloyed titanium. Table 9.4 [SCH92a] and Figure 9.1 show that the crevice corrosion resistance of Ti Gr 7, 12, 16, and 18 is enhanced relative to unalloyed titanium.

Itoh et al [ITO89] demonstrated the superior crevice corrosion resistance of Ti Gr 7 and Gr 12 relative to C.P. titanium (Ti Gr 3). Testing was conducted in boiling 20% NaCl and crevices were formed with a teflon grooved ring. Ti Gr 3 was susceptible to crevice corrosion at pH 6 and below, however Ti Gr 12 was not susceptible at pH 2 but was at pH 1.5, and Ti Gr 7 was not susceptible even at pH 1.5.

Schutz and Xiao [SCH93] performed a series of crevice corrosion tests on several palladium alloyed titanium alloys, including Ti Gr 16. Tests were conducted in acidic oxidizing chloride brines at temperature above 90°C (see Table 9.5). In each test Ti Gr 16 performance was equal to that of the higher alloyed Ti Gr 7.

Table 9.4. Crevice corrosion test data for Pd-containing titanium alloys in acidic oxidizing brines [SCH93]. Crevice attack frequency refers to number of occurrences of crevice corrosion per total number of crevices.

Test Environment	Alloy	Crevice Attack Frequency	Comments
20% NaCl / pH2 / 260°C (naturally-aerated)	Ti Gr 16	0 / 12	No attack
	Ti Gr 7	0 / 12	
	Ti Gr 18	0 / 12	
	Ti Gr 5 / Pd	0 / 12	
20% NaCl / pH2 / 90°C (Cl ₂ gas saturated)	Ti Gr 16	0 / 12	No attack
	Ti Gr 7	0 / 12	No attack
	Ti Gr 9	4 / 4	Significant attack
	Ti Gr 18	2 / 12	Borderline/incipient
	Ti Gr 5	12 / 12	Severe attack
	Ti Gr 5 / Pd	8 / 12	Mild. shallow attack
20% NaCl / pH1 / 90°C (Cl ₂ gas saturated)	Ti Gr 2	12 / 12	Severe attack
	Ti Gr 16	0 / 12	No attack
	Ti Gr 7	0 / 12	No attack
	Ti Gr 18	6 / 12	Shallow attack
	Ti Gr 5/Pd	12 / 12	Significant attack
Boiling 10% FeCl ₃ (pH 1.0-3.0) 102°C	Ti Gr 2	12 / 12	Severe attack
	Ti Gr 16	0 / 12	No attack
	Ti Gr 7	0 / 12	No attack
	Ti Gr 18	6 / 6	Significant attack
	Ti Gr 5 / Pd	6 / 6	Significant attack

Table 9.5. Incidence of crevice corrosion of titanium alloys in aerated saturated-NaCl solutions (PTFE gasket / metal crevices) [SCH93]. Data are incidences of crevice corrosion per total number of crevices.

Temp	100°C				200°C			
pH	2		6		2		6	
Test time (hr)	500	1000	500	1000	500	1000	500	1000
Ti Gr 2	4 / 4	4 / 4	4 / 4	4 / 4	4 / 4	---	4 / 4	---
Ti Gr 16 (0.05 Pd)	0 / 4	0 / 4	0 / 4	0 / 4	0 / 4	0 / 8	0 / 4	0 / 8
Ti Gr 7 (0.14 Pd)	0 / 4	0 / 4	0 / 4	0 / 4	0 / 4	0 / 8	0 / 4	0 / 8
Ti Gr 12	4 / 4	---	4 / 4	---	4 / 4	---	4 / 4	---

9.6 Surface Condition

Tighter crevices (smaller crevice gaps) enhance crevice corrosion attack, therefore flat, smooth metal surfaces enhance susceptibility relative to roughened surfaces. In creviced metal situations, ground or sandblasted surfaces are preferred relative to smooth heavily-pickled, or highly polished surfaces.

The presence of a thick thermal oxide film on commercially pure titanium will significantly enhance crevice corrosion resistance relative to thin oxide films [SCH81]. The same enhancement was not seen for anodized or pickled surfaces, although pickling removed iron contamination from the titanium surface. Testing for enhancement of crevice corrosion resistance of the more corrosion resistant titanium alloys (Ti Gr 7 and 12) was not performed. However, testing of these alloys in hot reducing acid solutions showed only short term benefits of thermal oxidation (done above 540°C), implying there would be no long term enhancement of crevice corrosion resistance by thermal oxidation. However, it should be mentioned that these tests were performed in very acidic solutions (1 to 15 wt.% HCl).

9.7 Metal potential

Impressed anodic potentials on titanium metal crevices will enhance the onset of crevice corrosion by promoting crevice acidification from the oxidation reaction : $2\text{Ti} + 2\text{HO}^- \rightarrow 2\text{TiO} + 2\text{H}^+ + 4\text{e}^-$. Although cathodic potentials may inhibit crevice corrosion below -0.4 V (vs. SCE), total cathodic protection may not be possible under severe crevice conditions.

10.0 SUSTAINED LOAD CRACKING

Sustained load cracking generally refers to the growth of sub-critical cracks under a static load at stress intensities less than K_{IC} (that stress necessary to cause cracks to grow without other influences). Terms such as "stable crack growth" or "slow crack growth", and "delayed cracking" are usually synonymous. In the present context, we are referring to sustained load cracking (SLC) as that affected by hydrogen present internally in titanium and its alloys. Other effects due to an external source of hydrogen will be discussed later.

There have been a number of studies of SLC in titanium alloys. High strength α / β titanium alloys have been found to be susceptible to sustained load subcritical crack growth in the absence of aggressive environment, including inert atmospheres. However there are very few observations of SLC in α -Ti alloys, the most frequently cited example being work by Paton [PAT74] who demonstrated hydride precipitation during SLC in a Ti-4%Al alloy containing as little as 100 ppm hydrogen. Since this hydrogen concentration is below the normally accepted limit of its solubility in this alloy, it was proposed that strain induced hydride precipitation was responsible for SLC. However, work on α / β Ti alloys, has shown SLC at even lower hydrogen contents. Williams [WIL74] tested a Ti-4%Al-3%Mo-1%V alloy containing 10 ppm hydrogen in both vacuum and moist air environment, and found SLC at stress intensities as low as 40% of the fracture toughness. It was concluded that the most plausible explanation of this was creep rather than hydrogen-induced cracking. A later study by Williams [WIL76] on a number of α / β Ti alloys showed that crack growth was quite sensitive to hydrogen content. Increasing hydrogen content reduced both

K_{IC} and the time to failure by cracking. Moreover, the threshold stress intensity for SLC varied with hydrogen content from a value of 27 $\text{MPa}\sqrt{\text{m}}$ at 7 ppm to 50 $\text{MPa}\sqrt{\text{m}}$ at 71 ppm. Williams attributes SLC to the effect of hydrogen on creep resistance, with possible interactions of metallurgical stability.

Meyn [MEY74], on the other hand, states that the occurrence of SLC is related to hydrogen content. He observed a decrease in the SLC threshold with increasing hydrogen contents up to 50 ppm. Further increases in hydrogen level resulted in increased growth rates while the threshold remained constant. Meyn also observed more rapid SLC growth in vacuum than in air for Ti-8Al-1Mo-1V, whereas Williams found no difference in growth rates in vacuum or air for Ti-8Al-1Mo-1V. Margolin [MAR76] proposed that SLC could be attributed to hydrogen in solution. He postulated that the simultaneous movement of a number of hydrogen atoms from one tetrahedral site to another, as could occur in the stress field ahead of the crack tip, could result in distortions that could produce a critical strain and nucleate a crack. Sandoz [SAN69] observed SLC in Ti-8Al-1Mo-1V alloy containing 14 to 50 ppm hydrogen. He also showed that the threshold stress intensity factor above which crack propagation began increased when specimens were vacuum annealed to reduce their hydrogen content. Boyer and Spurr [BOY78] also concluded that SLC is a function of hydrogen content and temperature in Ti-6Al-4V alloys containing 50-255 ppm hydrogen and showed that increasing the hydrogen content raises the temperature at which SLC will occur and increases the crack growth rate. They also concluded that hydride formation at the crack tip was an essential feature of the process.

It is evident from the foregoing that the mechanism of SLC in titanium alloys is not well understood. There seems little doubt that, in most cases, hydrogen plays a role, but there is considerable uncertainty as to whether the embrittlement is caused by hydrogen in solution or hydride precipitate, or both. Hydrides are difficult to detect, particularly if their volume fraction is small, and, in α/β Ti alloys, the hydrides precipitate preferentially at the α/β phase boundaries. On the other hand, observations of SLC at very low hydrogen contents (~ 10 ppm) are difficult to rationalize in terms of hydride cracking since hydrides would not be expected to be present. It should be emphasized, however, that hydrogen solubility limits are not precisely known, particularly in

α / β Ti alloys, and in addition, marked supersaturation effects can occur. Nuttal [NUT81] has compared the behavior of SLC in zirconium alloys and noted that α / β and some α -phase zirconium alloys are also susceptible to SLC. A model depending on the growth of hydrides is thought to account for these observations. Nuttal also suggests that in view of the many similarities between titanium and zirconium it might be expected that α -Ti alloys could be susceptible to SLC and the growth of hydride is thought to be critical.

Although the possibility of SLC exists, none has yet been observed in α -Ti alloys. For hydride precipitation to occur at temperatures in excess of 100°C, the hydrogen concentration would need to be relatively high. It should be noted that the maximum amount of hydrogen allowed during the manufacture of α -Ti alloys is 0.015 wt%.

11.0 Hydrogen Embrittlement

Hydrogen embrittlement of titanium alloys is of concern when the long-term integrity of titanium is a consideration [BRA80]. The susceptibility of all the α -Ti alloys to hydrogen embrittlement is a concern [MCK85]. Although α -Ti alloys might be expected to suffer from embrittlement by hydrogen when gaseously charged (at high temperatures) to high hydrogen levels [WIL62], the examination of titanium tubes removed from a steam condenser after more than 10 years of operation with an impressed current for cathodic protection suggests that titanium is very resistant to this form of deterioration under normal operating conditions, even in polluted sea water [COV76b].

The discussion of the participation of hydrogen in stress corrosion cracking (SCC) will be presented in Section 12.0. The present section is limited to a discussion of bulk hydride formation. However, some information presented may be useful in understanding hydrogen involvement in SCC.

11.1 Mechanism

Two types of hydrogen embrittlement have been proposed [WIL62]: impact embrittlement and low-strain-rate embrittlement. Impact embrittlement due to hydrogen is observed in the α -Ti alloys. The loss of ductility results from the presence of a brittle hydride phase in the alloy. Impact embrittlement becomes more severe with increased hydrogen content, increased strain rate, decreased temperature, and the presence of notches. At room temperature severe embrittlement can result from as little as 150 ppm hydrogen in notched specimens of unalloyed titanium. The α -Ti alloys are the most susceptible to impact embrittlement, but sufficient hydrogen content can result in impact embrittlement of β – and α / β - Ti alloys.

Low-strain-rate embrittlement by hydrogen has been reported most often in α / β Ti alloys, but α -Ti alloys and β -Ti alloys are also vulnerable [WIL62].

Susceptibility increases with increasing hydrogen content and decreasing strain rate. A region of maximum susceptibility exists near room temperature, with the region becoming broader with increasing hydrogen content. It should be noted that there is no low-strain-rate embrittlement at high strain rates, which distinguishes it from impact embrittlement.

Both types of embrittlement are thought to result from a decrease in solubility of hydrogen in titanium alloys with decreasing temperature [WIL62]. The difference in behavior between the type of embrittlement is related to differences in the kinetics of titanium hydride precipitation.

11.2 Physical Properties

In α -Ti and α -Ti alloys the solubility of hydrogen is low; being about 20-200 ppm at room temperature [PAT74]. Dilation of the α titanium lattice by absorbed hydrogen has been determined by x-ray lattice spacing measurement. At higher hydrogen concentrations, titanium hydride formation occurs. The hydride, or δ phase, is a stable ordered compound with composition range $\text{TiH}_{1.53}$ to $\text{TiH}_{1.99}$. The regions of α and δ phases stability are shown in the titanium-hydrogen phase diagram (Fig. 11.1) [MAS90]. Note the increase in

hydrogen solubility with increasing temperature. Determination of the hydrogen solubility in titanium is difficult because it is dependent on hydrogen pressure, stress, alloy composition, purity, and deformation [PAT74].

Titanium hydride has a CaF_2 crystal structure which consists of a face centered cubic arrangement of Ti ions with the hydrogen atoms located at the tetrahedral interstices. The lattice parameter of the fcc hydride phase is such that it has about 23 percent greater specific volume than α titanium. This large misfit results in non-coherent plate-shaped hydrides. A number of habit planes have been reported for titanium hydrides all of which correspond to possible slip or twinning planes in the alpha titanium lattice.

In β titanium, hydrogen solubility is considerably larger than it is in α titanium [PAT74]. For instance, more than 4000 ppm hydrogen are soluble in Ti-18Mo at room temperature. The body centered cubic lattice of the Ti-18Mo is expanded by 15% with the addition of 9000 ppm of hydrogen. Hydride formation in β -Ti alloys is not seen because at hydrogen concentrations above 10^4 ppm catastrophic failure occurs without the precipitation of hydrides.

Hydrogen diffusivity in α titanium is of the order of 10^{-10} to 10^{-11} cm^2/sec at 50°C . In the temperature range 25 - 100°C the diffusivity of hydrogen in α titanium has been reported to be [PAT74]:

$$D = 6 \times 10^{-2} \exp (-14,400 \pm 800 \text{ cal} / RT) \text{ cm}^2 / \text{s}.$$

A determination of the diffusivity in the temperature range 610 - 900°C gives a similar expression [PAP68]:

$$D = 3.0 \times 10^{-2} \exp (-14,700 \pm 650 \text{ cal} / RT) \text{ cm}^2 / \text{s}.$$

A slightly different expression for the diffusivity which was determined in the temperature range 500 - 824°C is given by [WAS54]:

$$D = 1.8 \times 10^{-2} \exp (-12,350 \text{ cal} \pm \text{cal} / RT) \text{ cm}^2 / \text{s}.$$

11.3 Effect of the Surface Layer on Hydrogen Uptake

The surface layer present on titanium greatly influences the rate of hydrogen uptake by titanium [TOM82]. The oxide layer provides a barrier to hydrogen uptake. For cathodic charging at low currents (2000 A/m²) polished specimens which were exposed to air prior to charging had a greater resistance to hydrogen uptake than those which were not exposed to air prior to charging. However this difference decreased with time and with increasing current density. This was due to the destruction of the protective oxide layer that formed upon exposure to air.

Surface preparation prior to oxidation also significantly influences the rate of hydrogen uptake [TOM82]. Etching of previous polished specimens prior to oxidation decreases the amount of hydrogen uptake by a factor of 10 at a charging current of 3000 Amps / m² after 5 hrs.

11.4 Effect of pH on Hydrogen Uptake

During cathodic polarization of α titanium at charging currents of 1.0 mA / cm², hydrogen absorption significantly decreases with increasing pH [PHI74]. For solutions of pH 0.3 and 1.3, the initial linear absorption rate becomes parabolic with increasing charging time. For solutions of pH 3.0, 4.6, and 7.3, decreasing linear rates of absorption were observed with increasing pH. For solutions of pH 10.3 and 14.0, no hydrogen absorption was detected. Similar results have been reported at higher charging currents (100 mA / cm²) [TOM82].

The rate-determining step in the hydrogen evolution reaction is believed to be electrochemical desorption [THO70]. Therefore, the number of adsorbed hydrogen atoms is expected to decrease with increasing pH producing a decrease of the amount of hydrogen absorbed. The minute amounts of hydrogen absorbed during charging in solutions of high pH may be explained by the stability of the oxide film [PAT74]. In the higher pH region a stable oxide film is expected to be present on titanium. This oxide film may act as a barrier to hydrogen absorption. In addition, there is a change in the discharge step of the hydrogen evolution reaction as pH increases. It changes from $\text{H}_3\text{O}^+ + \text{e}^- = \text{H}_{\text{ads}}$

+ H_2O to $\text{H}_2\text{O} + \text{e}^- = \text{H}_{\text{ads}} + \text{OH}^-$. This may affect the surface coverage of hydrogen atoms and thus the kinetics of hydrogen absorption.

11.5 Galvanic Coupling

In addition to gaseous hydrogen charging and electrochemical (cathodic) hydrogen charging, hydrogen absorption by titanium can be caused by galvanic coupling of titanium to a less noble material. Titanium galvanically coupled to aluminum in several aqueous electrolytes absorbs hydrogen, with the formation of surface hydrides [CHA68]. The electrolytes in the aqueous solutions were H_2SO_4 (pH 3.1), NH_4OH (pH 9.7), and 3.4 wt.% NaCl (pH 6.7). Hydrogen absorption occurred most readily in the acid solution. Surface preparation also significantly affected hydrogen uptake. Vapor blasted specimens offered the least resistance to hydrogen absorption, while etched specimens offered the most resistance.

Stressed specimens (U-bends) of titanium did not fail when galvanically coupled to aluminum in acid, basic, and salt solutions for 93 days [CHA68]. The stressed regions of the specimens absorbed more hydrogen than the unstressed regions. The hydride platelets which formed in the stressed region of the U-bends were oriented perpendicular to the tensile stress axis in the tension side, and they were oriented parallel to the stress axis in the compression side. This mode of precipitation is favored because the hydride is less dense than titanium.

A comprehensive study of cracking of both Ti Gr 2 and Gr 12 has been conducted by Clarke et al. [CLA86]. Using slow strain rate tests it was observed that the resistance to crack propagation of both grades is excellent in 3.5 % NaCl solution. However, the resistance of Ti Gr 12 breaks down under appropriate combinations of temperature and cathodic polarization. High cathodic polarization (to potentials below about -730mv (SHE)) and temperatures above 150°C are necessary to induce hydride cracking in Ti Gr 12. At most pH values, the free corrosion potential of titanium is well above the potential for hydrogen evolution and, hence, hydriding would not normally be

expected to occur without a significant amount of cathodic polarization, unless the conditions become highly acidic or basic.

The decisive factor for the occurrence of hydrogen embrittlement at lower temperatures is whether or not hydrogen is taken up by the metal. This will depend not only upon the generation of a sufficient hydrogen fugacity at the surface, but also on the ability of hydrogen to penetrate any passivating film formed there. Both factors will be very dependent upon the prevailing electrochemical conditions. Any radiolysis of the aqueous environment would also have a significant influence on the efficacy of hydrogen absorption by the metal [CLA86].

Hydrogen embrittlement has been suggested as a possible contributing factor to stress corrosion cracking (Section 12.0). One mechanism of stress corrosion cracking of titanium proposes that cracks propagate due to hydrogen embrittlement of the region in front of the crack. Other mechanisms involving different species have been suggested as the cause of stress corrosion cracking (see Section 12.0).

12.0 Stress Corrosion Cracking

Stress corrosion cracking (SCC) is a cracking phenomenon caused by the combined action of tensile stress, a susceptible alloy, and a corrosive environment. The metal normally shows no evidence of general corrosive attack, although slight localized attack in the form of pitting may be visible. Usually, only specific combinations of metallurgical and environmental conditions cause SCC. This is important, because it is often possible to eliminate or reduce SCC sensitivity by modifying either the microstructural characteristics of the metal or the makeup of the environment. Another important characteristic of SCC is the requirement that tensile stress be present. These stresses may be provided by cold work, residual stresses from fabrication, externally applied loads, and/or a combination of these factors.

Titanium alloys can be divided into two distinct classes depending on their susceptibility to SCC. The first class, which includes Ti Gr 2, 7, and 12, is

immune to SCC except in a few specific environments [SCH86]. These environments include anhydrous methanol / halide solutions, nitrogen tetroxide (N_2O_4), and red fuming HNO_3 . In these cases, a small amount of water will effectively inhibit against SCC. Ti Gr 2, 7, and 12 may also suffer liquid or solid metal embrittlement in contact with cadmium, silver, and possibly mercury.

High impurity (e.g. oxygen) concentrations in titanium alloys can cause susceptibility to SCC [DON88]. Curtis [CUR69] has shown that although Ti Gr 2 containing 0.12% oxygen is immune in 3.5 % NaCl solution using pre-fatigued bend specimens, a similar alloy containing 0.38% oxygen is susceptible to SCC. Donachie [DON88] has stated that an oxygen content of greater than 0.3% in unalloyed titanium is necessary for susceptibility to SCC. In addition at least one other study has shown a decrease in the fracture strength of notched bend specimens of C.P. titanium in sea water at room temperature [LAN66]. No service failures of C.P. titanium have been reported in aqueous chloride solutions [SCH86].

The SCC data accumulated at Sandia National Laboratories (SNL) [BRA80b, MOL83], Brookhaven National Laboratory (BNL) [AHN82], and by the Canadian Waste Management Program on Ti Gr 2 and 12 indicates that there is no SCC at naturally occurring potentials in various brines. This is based on the absence of both mechanical property degradation and slow crack growth. However, the fracture morphology near the periphery of certain fracture surfaces indicates a slight degree of embrittlement. It was suggested that the embrittlement was most likely caused by hydrogen, since titanium alloys are subject to hydrogen embrittlement (see Section 11.0).

Abrego et al. [ABR81] and Sorenson et al. [SOR85] also used the slow strain rate technique to examine the SCC behavior of Ti Gr 12 in brine and synthetic sea water at open circuit potentials. They concluded that there is no environmental effect on the mechanical properties of the alloy. However severe cathodic polarization resulted in a change in both fracture mode and macroscopic stress-strain behavior due to hydrogen absorption [SOR85].

The second class of titanium alloys, including the aerospace titanium alloys, has been found to be susceptible to several additional environments, most

notably aqueous chloride solutions. However, this susceptibility is associated with high stress concentrations typical of laboratory testing with loaded pre-cracked specimens, and generally is not observed with loaded smooth or notched specimens. In fact, the SCC susceptibility identified for these alloys is seldom observed in actual field applications.

Two mechanisms of SCC in titanium alloys are currently considered as plausible [MOL83]. One is that cracking is the result of hydrogen embrittlement. The other that cracking is the result of active dissolution at the crack tip. Absorbed hydrogen could result from material processing, electrochemical or chemical reactions during corrosion, and radiolysis of water. Property changes due to hydrogen may be alterations in the critical strain for fracture, fracture at hydride particles or at the interface between hydride and matrix, or hydride embrittlement by localized plastic deformation. Active (anodic) dissolution at the crack tip is thought to result from film formation and its subsequent rupture.

13.0 Galvanic Corrosion

Titanium, provided it is in its normal passive state, is usually the cathode when galvanically coupled to most commercial structural alloys in service, that is, its corrosion potential is noble relative to most other alloys (Table 13.1). Note that titanium's electrode potential is similar to stainless steel or nickel-base alloys (e.g. Alloy C and Monel 400) in the passive condition. Because of these small potential differences between these alloys negligible galvanic interactions can be expected provided passive conditions exist.

Table 13.1. Galvanic series in sea water flowing at 4 m/sec at 24°C [COT57].

Material	Steady State Electrode Potential (Volts vs. Saturated Calomel Electrode)
Graphite	0.25
Platinum	0.15
Zirconium	-0.04
316 Stainless Steel (passive)	-0.05
304 Stainless Steel (passive)	-0.08
Monel 400 (70Ni-30Cu)	-0.08
Alloy C	-0.08
Titanium	-0.10
Silver	-0.13
410 Stainless Steel (passive)	-0.15
316 Stainless Steel (active)	-0.18
Nickel	-0.20
430 Stainless Steel (passive)	-0.22
CDA 715 (70Cu-30Ni)	-0.25
CDA 706 (90Cu-10Ni)	-0.28
CDA 442 (admiralty brass)	-0.29
G Bronze	-0.31
CDA 687 (aluminum brass)	-0.32
Copper	-0.36
Alloy 464 (naval rolled brass)	-0.40
410 Stainless Steel (active)	-0.52
304 Stainless Steel (active)	-0.53
430 Stainless Steel (active)	-0.57
Carbon steel	-0.61
Cast iron	-0.61
Aluminum 3003-H	-0.79
Zinc	-1.03

In contrast, when titanium is galvanically coupled to a more active metal, anodic attack of the active metal occurs and hydrogen charging of titanium may occur. The rates of the reactions depend on several factors, including the relative cathode to anode areas, temperature, concentration of cathodic depolarizer (e.g. O_2 and H^+), solution flow velocity, and solution chemistry [SCH86]. Under appropriate conditions, active metals may include carbon steels, aluminum, zinc, copper alloys, or stainless steels which are active or pitting. In ambient sea water the corrosion rates of various copper alloys can be accelerated by up to factors of 5-10 when coupled to titanium (Fig. 13.1). In addition, high aqueous flow rates tend to accelerate galvanic copper alloy corrosion [SCH86].

Excessive cathodic hydrogen charging of titanium can occur if three conditions are met: 1) titanium is galvanically coupled to an active metal; 2) metal

temperature is above approximately 80°C, so that hydrogen diffusion into α titanium is significant; and 3) solution pH is greater than 12 or less than 3 [SCH86]. Very active metals, such as, zinc, magnesium, or aluminum, should not be coupled to titanium at above 80°C even in near-neutral solutions such as sea water. High concentrations of sulfides in aqueous solutions above 80°C also cause severe hydriding of titanium when the titanium is coupled to carbon steels or active stainless steel [COV79]. Under most conditions, copper or nickel-base alloys, and fully passive stainless steel alloys will not galvanically embrittle titanium [SCH86]. High temperature alkaline conditions may also result in excessive hydrogen uptake and embrittlement of titanium alloys.

There is a beneficial effect on titanium's protective oxide layer when it is galvanically coupled to those materials with more noble corrosion potentials [SCH86]. Graphite and various precious metals (e.g. Pt, Pd, Ru, and Ir) are such materials. In these couples titanium is the anodic member, which stabilizes its protective oxide film.

14.0 Radiation Environment

No published literature was found that concerns the corrosion of titanium alloys in radiation environments. However, there are reports that address the effects of a radiation field on various aqueous environments [RUP81]. Knowing the chemical changes that occur in a solution upon irradiation of the solution allows one to estimate the effects of solution irradiation by introducing the appropriate radiation-produced chemical species into the non-irradiated solution. This procedure is limited, however, because of the many short-lived reactive species (e.g. radicals) that exist during irradiation.

Several reports have addressed the effect of a radiation field on aqueous salt solutions [RUP81]. Radiolysis of brine produces $H^\cdot$, $\cdot OH$, e^-_{aq} , H_3O^+ , OH^- , H_2 , H_2O_2 , and HO_2 , with H_2 and H_2O_2 being the important stable molecular species. In addition, various oxychlorides and oxybromides may be formed. Chlorine ion (Cl_2^-) may also be an important transient species in this medium. Gases such as Cl_2 , Br_2 , and O_2 may also be produced in measurable amounts. If the gas-vapor phase contains N_2 , H_2 , CO_2 , Br_2 , Cl_2 , and O_2 , then irradiation

may produce some HCl, HBr, HNO₃, CO, O₃, NH₃, and various nitrogen oxides as products. The formation of these species is dependent on many factors including temperature, radiation dose rate, the amount of water present, and the ease of removal of the gases from solution.

15.0 Additional Corrosion Studies of Titanium

Smailos et al. [SMA87] studied the corrosion susceptibility of Ti-0.2%Pd and Alloy C-4 (a Ni-Cr-Mo alloy) in deaerated salt solutions at temperatures up to 170°C and durations of up to 500 days (Table 15.1). Under none of the test conditions was Ti-0.2%Pd susceptible to crevice corrosion. However, Alloy C-4 was susceptible to crevice corrosion under certain conditions. General corrosion rates of both alloys were comparable.

Gegner and Wilson [GEG59] compared the corrosion resistance of unalloyed titanium with unalloyed zirconium, Monel, and Alloy C-276 in various chloride salt solutions (Table 15.2). In each case titanium had better corrosion resistance than the other materials tested.

The corrosion performance of Ti Gr 7 and 12 in various environments not covered elsewhere in this report is given in Appendix A.

Table 15.1. Crevice and general corrosion of Ti-0.2%Pd and Alloy C-4 in a deaerated brine solution [SMA87].

Material	Crevice Type	Surface Condition	Temperature / Time	Maximum Crevice Corrosion Depth (μm)	Radiation
Ti - 0.2%Pd	Metal/PTFE	As received	90°C / 582 d	no attack	No
	Metal/Metal	As received	90°C / 489 d	no attack	No
			170°C / 286 d	no attack	No
Alloy C-4	Metal/Metal	Polished	90°C / 266 d	no attack	No
			170°C / 266 d	no attack	No
	Metal/PTFE	As received	90°C / 582 d	250	No
	Metal/Metal	As received	90°C / 489 d	70	No
			170°C / 286 d	non-uniform corrosion; black corrosion product	No
	Metal/Metal	Polished	90°C / 266 d	20	No
			170°C / 266 d	-	No

Material	Temperature (°C)	Exposure time (d)	Weight loss (g/m)	Corrosion rate ($\mu\text{m/a}$)
Ti-0.2%Pd	90	559	1.2 $\pm$ 0.07	0.17 $\pm$ 0.03
	170	529	0.46 $\pm$ 0.07	0.07 $\pm$ 0.03
	200	540	0.97 $\pm$ 0.07	0.14 $\pm$ 0.03
Alloy C-4	90	559	0.26 $\pm$ 0.07	0.02 $\pm$ 0.02
	170	368	1.48 $\pm$ 0.07	0.17 $\pm$ 0.02
	200	540	2.69 $\pm$ 0.07	0.21 $\pm$ 0.02

Table 15.2. Exposures of various metals to salt solutions [GEG59].

Environment	Temp (°C)	Duration (days)	Ti	Zr	Monel	Alloy C
Sea water sat'd w/ CO	24	160	0.003	0.01	4	—
Sea water; very high velocity	24	212	nil	0.05	172, ⁵	—
Sat'd NaCl brine; pH 10.4	57	125	nil	0.001	0.08 ⁶	nil
Sat'd NaCl Brine	21	208	nil	0.004	0.6 ⁶	nil
Sat'd NaCl Brine	60	169	0.0006	0.007	0.05 ⁶	0.002 ⁶
Sat'd KCl Brine	60	183	0.0002	0.009	0.02 ⁶	0.002
Sat'd NaCl brine	71	163	nil	0.01	0.04 ⁶	0.02
20% NaCl brine; pH 2.0-4.5	74	73	0.01	19 ^{5,8}	>90 ¹	12; 0.1 ⁹

- 1) Specimens were completely consumed during the test.
- 2) One of two duplicate specimens was lost.
- 3) Shallow or slight pitting attack.
- 4) Moderate pitting attack.
- 5) Severe pitting attack.
- 6) Slight attack under spacer.
- 7) Moderate attack under spacer.
- 8) Sever attack under spacer.
- 9) One of two specimens suffered severe pitting and under-spacer attack.

16.0 SUMMARY

Of the materials reviewed, commercially pure titanium, Ti Gr 2, is the most susceptible to crevice corrosion. Ti Gr 7, 12, and 16 are likely to be very resistant to crevice corrosion under the current expected Yucca Mountain repository conditions. Although Grade 7 has the greatest resistance to crevice corrosion it is also the most expensive.

Although the possibility of SLC exists, it has not yet been observed in α Ti alloys. For hydride precipitation to occur at temperatures in excess of 100°C, the hydrogen concentration would need to be relatively high, much higher than the maximum amount of hydrogen allowed during the manufacture of α Ti alloys (0.015 wt%).

A large amount of SCC data accumulated at SNL and BNL for the WIPP program and by the Canadian Waste Management Program on titanium grades 2 and 12 indicates that there is no SCC at naturally occurring potentials in various brines.

Hydride induced cracking of titanium is a possibility and therefore, further investigation of this phenomenon under credible repository conditions is warranted.

One disadvantage of titanium and its alloys is that their strengths decrease rather rapidly with temperature. This is due to the strong temperature dependence of interstitial solute strengthening mechanisms.

In view of the above, Ti Gr 12 and 16 are recommended for further consideration as candidate materials for high level nuclear waste containers.

---

*Work performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract W-7405-ENG-48.

17. 0 References

- ABR81 L. Abrego and H.L. Rack, "The Slow Strain Rate Behaviour of TiCode 12(ASTM Gr.12) in Aqueous Chloride Solutions", CORROSION/81, NACE, Houston Texas, 1981.
- AHN82 T.M. Ahn and P. Soo, "Container Assessment-Corrosion Study of HLW Container Materials, Quarterly Progress Report, Oct-Dec 1981," NUREG/Cr-2317, BNL-NUREG-51499, i (4), Brookhaven National Laboratory (April 1982)
- AND64 V.V. Andreeva, "Behavior and Nature of Thin Oxide Films on Some Metals in Gaseous Media and in Electrolyte Solutions," Corrosion, Vol. 20, 1964, pp. 35t-46t.
- BOY78 R.R. Boyer and W.F. Spurr, "Characteristics of Sustained-Load Cracking and Hydrogen Effects in Ti-6Al-4V," Metallurgical Transactions A, Vol. 9A, 1978, pp. 23-29.
- BOY85 R.R. Boyer, "Titanium and Titanium Alloys," in **Metals Handbook 9th Edition, Vol. 9, Metallography and Microstructures**, American Society for Metals, Metals Park, Ohio, 1985, pp. 458-475.
- BRA80 J.W. Braithwaite and M.A. Molecke, "Nuclear Waste Canister Corrosion Studies Pertinent to Geologic Isolation," Nuclear and Chemical Waste Management, Vol. 1, 1980, pp. 37-50.
- BRA80b J.W. Braithwaite, N.J. Magnami, and J.W. Munford, "Titanium Alloy Corrosion in Nuclear Waste Environments," Sandia Laboratories CONF-800305--5, 1980.
- CHA68 L.A. Charlot and R.E. Westerman, "Low-Temperature Hydriding of Zircaloy-2 and Titanium in Aqueous Solutions," Electrochemical Technology, Vol. 6, No. 3-4, 1968, pp. 132-137.
- CLA86 C.F. Clarke, D. Hardie, and P. McKay, "The Cracking of Titanium in Hot Aqueous Sodium Chloride Solutions," Corrosion Science, Vol. 26, No. 6, 1986, pp. 425-440.
- COT57 J.B. Cotton and B.P. Dowing, "Corrosion Resistance of Titanium to Seawater," Trans. Inst. Marine Engineering, Vol. 69, No. 8, 1957, pp. 311.
- COV76 L.C. Covington, "Pitting Corrosion of Titanium Tubes in Hot Concentrated Brine Solutions," **Galvanic and Pitting Corrosion-Field and Laboratory Studies, ASTM STP 576**, ASTM, Philadelphia, Pennsylvania, 1976, p. 147

- COV76b L.C. Covington, W.M. Parris, and D.M. McCue, CORROSION/76, Paper 79, NACE, Houston, Texas, 1976.
- COV77 L.C. Covington, "Titanium Solves Corrosion Problems in Petroleum Processing," Metal Progress, Vol. 111, No. 2 (Feb 1977) pp. 38-45.
- COV79 L.C. Covington, "The Influence of Surface Condition and Environment on the Hydriding of Titanium," Corrosion, Vol 35, No. 8, 1979, pp. 378-382.
- COV89 L.C. Covington and P.A. Schweitzer, "Titanium," in **Corrosion and Corrosion Protection Handbook, Second Edition**, P.A. Schweitzer, ed., Marcel Dekker, Inc., New York, 1989, Chap. 10.
- CUR69 R.E. Curtis, R.R. Boyer, and J.C. Williams, "Relationship Between Composition, Microstructure, and Stress Corrosion Cracking (in Salt Solutions) in Titanium Alloys," Trans. ASM Vol. 62, p. 457, 1969.
- DON88 M.J. Donachie, **Titanium; A Technical Guide**, ASM International, Metal Park, Ohio, 1988.
- FEI70 N.G. Feige and R.L. Kane, "Experience with Titanium Structures in Marine Service," Materials Protection and Performance, Vol. 9, No. 8, Aug. 1970, pp. 13.
- GEG59 P.J. Gegner and W.L. Wilson, "Corrosion Resistance of Titanium and Zirconium in Chemical Plant Exposures," Corrosion, Vol. 15, No. 7, July 1959, pp. 341t-350t.
- GRI68 J.C. Griess, "Crevice Corrosion of Titanium in Aqueous Salt Solutions," Corrosion, Vol. 24, No. 4, April 1968, pp. 96-109.
- IKE90 B.M. Ikeda, et al., "The Effect of Temperature on Crevice Corrosion of Titanium," Proceedings of the 11th International Corrosion Congress, Vol. 5, Florence, Italy, April 1990.
- ITO89 H. Itoh, K. Kitaoka, Y. Tsumori, H. Satoh, and T. Furuya, "Crevice Corrosion Resistance and Mechanical Properties of ASTM Grade 12 Titanium Alloy," KOBELCO Technol. Rev., Vol. 6, 1989, pp. 41-45.
- KOI73 T. Koizumi and S. Furuya, "Pitting Corrosion of Titanium in High Temperature Halide Solutions," Proc. 2nd Int. Conf. Titanium Sci. Technol., Plenum, New York, 1973, pp. 2383-2393.
- LAM90 S. Lampman, "Wrought Titanium and Titanium Alloys," **Metals Handbook, 10th Edition; Vol. 2, Properties and Selection: Nonferrous Alloys and Special-Purpose Materials**, ASM International, 1990, pp. 592-633.

- LAN66 I.R. Lane, J.L. Cavallaro, and A.G.S. Morton, "Sea Water Embrittlement of Titanium," in **Stress Corrosion Cracking of Titanium**, ASTM STP 397, 246, 1966.
- LEE81 J.B. Lee, "Elevated Temperature Potential - pH Diagrams for the Cr-H₂O, Ti-H₂O, Mo-H₂O, and Pt-H₂O Systems," Corrosion, Vol. 37, No. 8, Aug. 1981, pp. 467-481.
- MAR76 H. Margolin, "Stress, Hydrogen Segregation, and Fracture in α/β Titanium Alloys," Metallurgical Transactions A, Vol. 7A, 1976, pp. 1233-1235.
- MAS90 T.B. Massalski, editor-in-chief, **Binary Alloys Phase Diagrams; Second Edition**, ASM International, 1990, pp. 2675-2679, 2874-2876, 3058-3060.
- MAT84 H. Mattsson and I. Olefjord, "General Corrosion of Ti in Hot Water and Water Saturated Bentonite Clay," SKB Technical Report 84-19, Swedish Nuclear Fuel and Waste Management Co., Stockholm, Dec. 1984.
- MAT85 H. Mattsson and I. Olefjord, "ESCA Investigation of the Reaction Products Formed on Titanium Exposed to Water Saturated Bentonite Clay," in Scientific Basis for Nuclear Waste Management IX, L.O. Werme, ed., Materials Research Society Symposium, Vol. 50, 1985, pp. 481-490.
- MCC95a R.D. McCright, "Scientific Investigation Plan, Metallic Barriers, WBS 1.2.2.5.1," to be published.
- MCC95b R.D. McCright, "Updated Candidate List for Engineered Barrier Materials," UCRL-ID 119442, to be published.
- MCK84 P. McKay, "Crevice Corrosion of Ti - 0.8% Ni - 0.3% Mo Alloy (ASTM Grade-12 in Chloride Environments at Elevated Temperature," Proceedings of the 9th International Congress on Metallic Corrosion, June 1984, Vol. 3, National Research Council of Canada, Ottawa, Canada, pp. 288-297.
- MCK85 P. McKay and D.B. Mitton, "An Electrochemical Investigation of Localized Corrosion on Titanium in Chloride Environments," Corrosion, Vol. 41, No. 1, Jan. 1985, pp. 52-62.
- MEY74 D.A. Meyn, "Effect of Hydrogen on Fracture and Inert-Environment Sustained Load Cracking Resistance of α/β Titanium Alloys", Metallurgical Transactions, Vol. 5, Nov. 1974, pp. 2405-2414.
- MIN78 W.W. Minkler, "Titanium for Chemical Processing Equipment," Metal Progress, Vol. 113, No. 2 (Feb 1978), pp. 27-31.

- MOL83 M.A. Molecke, J.A. Rupen, and R.N. Diegle, "Materials for High-Level Waste Canister/Overpacks in Salt Formations," Nuclear Technology, Vol. 63, Dec. 1983, pp. 476-506.
- NUT81 K. Nuttall and V.F. Urbanic, "An Assessment of Materials for Nuclear Fuel Immobilization Containers", AECL-6440, Whiteshell Nuclear Research Establishment, Manitoba, September 1981.
- OET76 T.P. Oettinger and M.G. Fontana, "Austenitic Stainless Steel and Titanium for Wet Oxidation of Sewage Sludge," Materials Performance, Vol. 15, No. 11, Nov. 1976, pp. 29-35.
- OLD78 J.W. Oldfield and W.H. Sutton, "Crevice Corrosion of Stainless Steels; I. A Mathematical Model," British Corrosion Journal, Vol. 13, 1978, pp. 13-22.
- PAP68 T.P. Papazoglou and M.T. Hepworth, "The Diffusion of Hydrogen in Titanium," Trans. of the Metallurgical Society of AIME, Vol. 242, April 1968, pp. 682-685.
- PAT74 N.E. Paton and J.C. Williams, "Effect of Hydrogen on Titanium and Its Alloys," **Hydrogen in Metals**, I.M. Bernstein, A.W. Thompson, eds., American Society for Metals, 1974, pp. 409-432.
- PET80 J.A. Petit, G. Chatainier, P. Lafargue, and F. Dabosi, "Electrochemical Behaviour of Titanium-Nickel Alloys in Sulfuric Acid Media," in Titanium 80, Vol. 4, Science and Technology, Proceedings of the 4th International Conference on Titanium, Kyoto, Japan, May 19-22 (1980), The Metallurgical Society of AIME, pp. 2659-2667.
- SAE93 Society of Automotive Engineers, **Metals & Alloys in the Unified Numbering System**, Society of Automotive Engineers, 1993, pp 241-245.
- SAN69 G. Sandoz, Proceedings of Conference on Fundamental Aspects Of Stress Corrosion, p. 689, NACE, Houston, 1969.
- SCH56 D. Schlain and C.B. Kenahan, "The Role of Crevices in Decreasing the Passivity of Titanium in Certain Solutions", Corrosion, Vol. 12, No. 8, Aug. 1956, pp. 422t-426t.
- SCH81 R.W. Schutz and L.C. Covington, "Effect of Oxide Films on the Corrosion Resistance of Titanium," Corrosion, Vol 37, Oct. 1991, pp. 585-591.
- SCH85 R.W. Schultz, Materials Performance, Vol. 24, No. 1, 1985, pp. 39-47.
- SCH86 R.W. Schultz, "Titanium," Process Industries Corrosion, National Association of Corrosion Engineers, Houston, 1986, pp. 503-526.

- SCH87 R.W. Schutz and D.E. Thomas, "Corrosion of Titanium and Titanium Alloys," in **ASM Metals Handbook, 9th Edition, Vol. 13, Corrosion**, ASM International, Materials Park, Ohio, 1987, pp. 669-706.
- SCH92a R.W. Schutz, "Understanding and Preventing Crevice Corrosion of Titanium Alloys; Part I," *Materials Performance*, Oct. 1992, pp. 57-62.
- SCH92b R.W. Schutz, "Understanding and Preventing Crevice Corrosion of Titanium Alloys; Part II," *Materials Performance*, Nov. 1992, pp. 54-56.
- SCH93 R.W. Schutz and M. Xiao, "Optimized Lean-Pd Titanium Alloys for Aggressive Reducing Acid and Halide Service Environments," 12th International Corrosion Congress, Houston, TX, Sept. 1993, National Association of Corrosion Engineers.
- SED72 A.J. Sedriks, J.A.S. Green, and D.L. Novak, "Electrochemical Behavior of Ti-Ni Alloys in Acidic Chloride Solutions," *Corrosion*, Vol. 28, No. 4, April 1972, pp. 137-142.
- SHI78 K. Shimogori, H.Sato, and H.Tomari, "Crevice Corrosion of Titanium in NaCl Solutions in the Temperature Range 100 to 250°C," *J.of the Japan Institute of Metals*, Vol. 42, 1978, pp. 567-572.
- SOR85 N.R. Sorensen and J.A. Ruppen, "The Environmental Cracking of Ticode-12 in Aqueous Chloride Environments," *Corrosion*, Vol. 41, No. 10, Oct. 1985, pp. 560-569.
- SMA87 E. Smailos, W. Schwarzkopf, R. Koster, "Corrosion Behavior of Container Materials for the Disposal of High-Level Waste forms in Rock Salt Formations," Report # KfK 4265 (ISSN 0303-4003), May 1987.
- SMA81 R.E. Smallwood, ASTM STP728, American Society for Testing and Materials, 1981, pp. 147-162.
- THO70 N.T. Thomas and K. Nobe, "Kinetic of the Hydrogen Evolution Reaction on Titanium," *J. of the Electrochemical Society*, Vol. 117, No. 5, May 1970, pp. 622-626.
- TOM82 N.D. Tomashov, G.P. Chernova, V.I. Kasarin, E.G. Mansky, T.A. Fedoseeva, V.V. Krasnoyarsky, and T.P. Stepanova, "Corrosion and Passivity of The Cathode-Modified Titanium-Based Alloys," **Titanium and Titanium Alloys - Scientific and Technological Aspects**, Vol. 2, J.C. Williams, A.F. Belov, eds., Plenum Press, New York, 1982, pp. 915-925.

- WAS54 R.J. Wasilweski and G.L. Kehl, "Diffusion of Hydrogen in Titanium," *Metallurgica*, Vol. 50, Nov. 1954, pp. 225-230.
- WIL74 D.N. Williams, "Subcritical Crack Growth Under Sustained Load," *Metallurgical Transactions*, Vol. 5, 1974, pp. 2351-2358.
- WIL76 D.N. Williams, "Effects of Hydrogen in Titanium Alloys on Subcritical Crack Growth Under Sustained Load", *Materials Science and Engineering*, Vol. 24, 1976, pp. 53-63.
- WIL62 D.N. Williams, "The Hydrogen Embrittlement of Titanium Alloys," *J. of the Institute of Metals*, Vol. 91, 1962-63, pp. 147-152.

Appendix A. General Corrosion Data for Titanium Alloys [SCH87]

Medium	Alloy	Concentration (%)	Temperature (°C)	Corrosion Rate (mm/yr)
Acetic acid + 5% formic acid	Gr 12	58	Boiling	nil
Ammonium hydroxide	Gr 12	30	Boiling	nil
Aluminum chloride	Gr 12	10	Boiling	nil
	Gr 7	10	100	<0.025
	Gr 7	25	100	0.025
Ammonium chloride	Gr 12	10	boiling	nil
Aqua regia	Gr 7	3:1	Boiling	1.12
	Gr 12	3:1	Boiling	0.61
Calcium chloride	Gr 7	62	150	nil
	Gr 7	73	177	nil
Chlorine, wet	Gr 7	---	25	nil
Chromic acid	Gr 7	10	Boiling	nil
Citric acid	Gr 7	50	Boiling	0.025
	Gr 12	50	Boiling	0.013
Ferric chloride	Gr 7	10	Boiling	nil
	Gr 12	10	Boiling	nil
	Gr 7	30	Boiling	nil
Formic acid	Gr 7	45	Boiling	nil
	Gr 12	45, 50	Boiling	nil
	Gr 7	50	Boiling	0.01
	Gr 12	90	Boiling	0.56
	Gr 7	90	Boiling	0.056
Hydrochloric acid, deaerated	Gr 7	3	82	0.013
	Gr 7	5	82	0.051
	Gr 7	10	82	0.419
Hydrochloric acid	Gr 7	0.5	Boiling	nil
	Gr 7	1.0	Boiling	0.008
	Gr 7	1.5	Boiling	0.03
	Gr 7	5.0	Boiling	0.23
	Gr 12	0.5	Boiling	nil
	Gr 12	1.0	Boiling	0.04
	Gr 12	1.5	Boiling	0.25

Hydrochloric acid, hydrogen saturated	Gr 7	1-15	25	<0.025
	Gr 7	20	25	0.102
	Gr 7	5	70	0.076
	Gr 7	10	70	0.178
	Gr 7	15	70	0.33
	Gr 7	3	190	0.025
	Gr 7	5	190	0.102
	Gr 7	10	190	8.9
Hydrochloric acid, oxygen saturated	Gr 7	3, 5	190	0.127
	Gr 7	10	190	9.3
Hydrochloric acid, chlorine saturated	Gr 7	3,5	190	<0.03
	Gr 7	10	190	29.0
Hydrochloric acid, aerated	Gr 7	1, 5	70	<0.03
	Gr 7	10	70	0.05
	Gr 7	15	70	0.15
Hydrochloric acid + 4%FeCl ₃ + 4% MgCl ₂	Gr 7	19	82	0.49
Hydrochloric acid + 4%FeCl ₃ + 4% MgCl ₂ , chlorine saturated	Gr 7	19	82	0.46
Hydrochloric acid + 5 g/l FeCl ₃ + 16 g/l FeCl ₃ + 16 g/l CuCl ₂	Gr 7	10	Boiling	0.279
	Gr 7	10	Boiling	0.076
	Gr 7	10	Boiling	0.127
Hydrochloric acid + 2 g/l FeCl ₃ + 0.1% FeCl ₃ + 0.1% FeCl ₃	Gr 12	4.2	91	0.058
	Gr 7	5	Boiling	0.013
	Gr 12	5	Boiling	0.020
Hydrochloric acid + 18% H ₃ PO ₄ + 5% HNO ₃	Gr 7	18	77	nil
Hydrogen peroxide pH 1 pH 4 pH 1 pH 4 + 500 ppm Ca ²⁺ , pH 1 + 500 ppm Ca ²⁺ , pH 1	Gr 7	5	23	0.062
	Gr 7	5	23	0.010
	Gr 7	5	66	0.127
	Gr 7	5	66	0.046
	Gr 7	5	66	nil
	Gr 7	20	66	0.76

Hydrogen peroxide, pH 1 + 5% NaCl	Gr 7	20	66	0.008
Magnesium chloride	Gr 7	Saturated	Boiling	nil
Oxalic acid	Gr 7	1	Boiling	1.14
Phosphoric acid, naturally aerated	Gr 12	25	25	0.019
	Gr 12	30	25	0.056
	Gr 12	45	25	0.157
	Gr 12	8	52	0.02
	Gr 12	13	52	0.066
	Gr 12	15	52	0.52
	Gr 12	5	66	0.038
	Gr 12	7	66	0.15
	Gr 12	0.5	Boiling	0.071
	Gr 12	1.0	Boiling	0.14
	Gr 7	40	25	0.008
	Gr 7	60	25	0.07
	Gr 7	15	52	0.036
	Gr 7	23	52	0.15
	Gr 7	8	66	0.076
	Gr 7	15	66	0.104
	Gr 7	0.5	Boiling	0.050
	Gr 7	1.0	Boiling	0.107
	Gr 7	5.0	Boiling	0.228
Sodium flouride pH 7 pH 7	Gr 12	1	Boiling	0.001
	Gr 7	1	Boiling	0.002
Sodium sulfate, pH 1	Gr 7	10	Boiling	nil
Sulfamic acid	Gr 12	10	Boiling	11.6
	Gr 7	10	Boiling	0.37
Sulfuric acid, naturally aerated	Gr 12	9	24	0.003
	Gr 12	9.5	24	0.006
	Gr 12	10	24	0.38
	Gr 12	3.5	52	0.013
	Gr 12	3.75	52	1.73
	Gr 12	2.75	66	0.015
	Gr 12	3.0	66	1.65
	Gr 12	0.75	Boiling	0.003
	Gr 12	1.0	Boiling	0.91
	Gr 7	1.0	204	0.005
	Gr 7	2.0	204	nil
	Gr 12	1.0	204	0.91
Sulfuric acid, nitrogen saturated	Gr 7	5	70	0.15
	Gr 7	10	70	0.25
	Gr 7	1, 5	190	0.13
	Gr 7	10	190	1.50

Sulfuric acid, oxygen saturated	Gr 7	1-10	190	0.13
Sulfuric acid, chlorine saturated	Gr 7	10	190	0.051
	Gr 7	20	190	0.38
Sulfuric acid, nitrogen saturated	Gr 7	10	25	0.025
	Gr 7	40	25	0.23
Sulfuric acid, aerated	Gr 7	10	70	0.10
	Gr 7	40	70	0.94
Sulfuric acid + 5 g/l $\text{Fe}_2(\text{SO}_4)_3$	Gr 7	10	Boiling	0.178
Sulfuric acid + 16 g/l $\text{Fe}_2(\text{SO}_4)_3$	Gr 7	10	Boiling	<0.03
Sulfuric acid + 16 g/l $\text{Fe}_2(\text{SO}_4)_3$	Gr 7	20	Boiling	0.15
Sulfuric acid + 15% CuSO_4	Gr 7	15	Boiling	0.64
Sulfuric acid + 1% CuSO_4	Gr 7	30	Boiling	1.75
Sulfuric acid + 100 ppm Cu^{2+} + 1% thiourea (deaerated)	Gr 7	1	100	nil
	Gr 12	1	100	0.23
Sulfuric acid + 1000 ppm Cl^-	Gr 7	15	49	0.015

J.L. Murray, 1987.

Fig. 2.1. Palladium-titanium phase diagram [MAS90].

J.L. Murray, 1991.

Fig. 2.2. Nickel-titanium phase diagram [MAS90].

J.L. Murray, 1987.

Fig. 2.3. Molybdenum-titanium phase diagram [MAS90].

Fig. 3.1. Minimum tensile strength of low-strength titanium alloys [LAM90].

Fig. 6.1. Pourbaix diagrams for Ti-H₂O at 25, 150, and 300°C [LEE81].

Fig. 9.1. Temperature - pH limits for crevice corrosion of titanium alloys in concentrated NaCl brines [SCH85].

Obtained from a P - T - X surface.

A. San-Martin and F.D. Manchester, 1987.

Fig. 11.1. Hydrogen-titanium phase diagram [MAS90].

Fig. 13.1. Enhanced corrosion of various copper alloys when galvanically-coupled to titanium in ambient temperature seawater [SCH86].