DOE/PC/93215--T6

**NOVEL MICROORGANISM FOR SELECTIVE SEPARATION
OF COAL FROM ASH AND PYRITE**

DOE Grant No. DE-FG22-93PC93215

Sixth Quarterly Technical Progress Report
(January 1, 1995 - March 31, 1995)

Submitted by

Professor Manoranjan Misra (PI)
Professor Ross W. Smith (Co-PI)
Ashok M. Raichur (Graduate Student)

Department of Chemical and Metallurgical Engineering
Mackay School of Mines
University of Nevada, Reno
Reno, NV 89557

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

RECEIVED
JSDOE/PETC
95 MAY -1 PM 3:16
ACQUISITION & ASSISTANCE DIV.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

na

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TABLE OF CONTENTS

SUMMARY	1
INTRODUCTION	2
EXPERIMENTAL PROCEDURES	2
Cultivation of <i>Mycobacterium phlei</i>	2
Sedimentation and Flocculation Experiments	3
Floc Separation	3
RESULTS AND DISCUSSION	4
Sedimentation and Flocculation Experiments	4
Floc Separation	6
DLVO Calculations	8
FUTURE WORK	13
REFERENCES	14

SUMMARY

This report summarizes the progress made during the sixth quarter of the research project entitled "A Novel Microorganism for Selective Separation of Coal from Ash and Pyrite", DOE Grant No. DE-FG22-93PC93215.

The objective of this research project is to study the effectiveness of a novel hydrophobic microorganism, *Mycobacterium phlei* (*M. phlei*), for the selective flocculation of coal from pyrite and ash forming minerals. During the reporting period, the flocculation efficiencies of Illinois No.6 and KY No.9 coal in the presence of whole and ruptured cells of *M. phlei* were studied. The effect of synthetic flocculants were also studied for comparison at selected pH values. Results showed that the whole cells of *M. phlei* can flocculate coal very effectively and rapidly for both the coal samples. However, with ruptured cells of *M. phlei* the flocculation efficiency is significantly less which can be attributed to the loss of extracellular surfactants during rupturing. Separation of flocs using column flotation was studied for both the coal samples in the acidic pH range. Results indicated that excellent rejection of pyritic sulfur and ash could be obtained with a high combustible recovery. DLVO calculations were performed for all the minerals used in this study to calculate the interaction energies in the presence of whole cells and ruptured cells of *M. phlei*. A minimum in interaction energy is observed between coal and whole cells of *M. phlei* at pH 4 which is probably responsible for the higher adhesion and flocculation efficiencies at that pH. However, with ruptured cells the interaction energy increases thus decreasing the amount of *M. phlei* cells adhering to the surface.

INTRODUCTION

The selective separation of pyrite and ash-forming minerals from coal can be accomplished by flotation, agglomeration and selective flocculation. The methods currently used for selective flocculation of coals include addition of natural or synthetic polymeric flocculants along with precise pH control. In some cases, these flocculants are nonselective or work imperfectly. It is known that many highly charged planktonic algae and bacteria will adhere to certain solid surfaces if the charge or hydrophobic interaction between the organism and the solids are favorable for adhesion. The resultant microorganism-mineral entities, if formed, can flocculate and can be separated. In addition, many living organisms produce extracellular biopolymers that can also cause flocculation. The microorganism, *M. phlei*, has the properties of being both highly charged and highly hydrophobic. The aim of the present investigation is to study the effectiveness of *M. phlei* and biopolymers derived from the organism for selective flocculation and separation of fine coal from pyrite and ash.

EXPERIMENTAL PROCEDURES

1. Cultivation of *Mycobacterium phlei*

The freeze dried culture of microorganism, *M. phlei*, was first transferred to a rehydration medium (supplied by Carolina Biological Supply Company) and incubated at 35°C for 48 hours. *M. phlei* was grown in a culture medium consisting of the following : 10 g/l D-(+)-glucose, 1 g/l beef extract, 1 g/l yeast extract, and 2 g/l enzymatic hydrolysate casein. The above materials were supplied by Sigma Chemical Company, St. Louis, MO. The culture medium was sterilized at 121°C for 25 minutes in a Spectroline Model 750 autoclave. The sterilized culture medium was cooled and the incubated bacteria was inoculated into the medium. Culturing was carried out in 250 ml flasks continuously shaken at 150 rpm at 35°C in a G24 Environmental incubator shaker (New Brunswick Scientific Co. Inc., NJ). After about 30 hours of culturing, *M. phlei* suspension was filtered using a 0.45 mm Millipore filter paper, washed twice and then resuspended in distilled water. Sterilized

glassware and distilled water were used throughout the investigation.

2. Sedimentation and Flocculation Experiments

Sedimentation and flocculation tests were performed in a 11.5" tall graduated cylinder with a volume of 500 ml. A 2% solids slurry consisting of minus 325 mesh size particles was conditioned and pH adjusted. After pH adjustment, flocculant was added slowly and the suspension was stirred using a Phipps and Bird paddle stirrer at 250 rpm for 1 minute. Further conditioning was done for 2 minutes at 50 rpm to allow for initial floc growth to take place. Then the suspension was transferred to the graduated cylinder. Samples were taken from the bottom outlet after predetermined time intervals. The suspensions were filtered, dried and weighed.

For the sedimentation tests, the amount of material settling through the top 10" of the cylinder was used as the criteria for determining settling rates. The results of flocculation tests are reported here in terms of flocculation efficiency (E_f) which is defined as :

$$E_f = \frac{(W_{so} - W_{sf})}{W_{so}} \quad (1)$$

where W_{so} represents the weight of the solids in a given volume of the suspension before the addition of flocculant and W_{sf} represents the same after addition of flocculant. When $W_{so} = W_{sf}$, no flocculation occurs and $E_f = 0$. When $W_{sf} = 0$, $E_f = 1$, indicating that the flocculant is effective. E_f can be negative, in which case the flocculant acts as a dispersant.

3. Floc Separation

Floc separation studies were performed using a laboratory scale column flotation cell. The setup consisted of a column with a working volume of 320 ml. Nitrogen gas was passed at the bottom at the required flow rate. Flow rate of gas was controlled using a Gilmont No.13 flow meter. After flocculation, the entire slurry was transferred to the flotation cell. No pH adjustments were

done at this stage. Required amount of frother (MIBC) was added and flotation was carried out for 5 minutes at the required flow rate. The float and tail were filtered, dried, weighed and analyzed.

Baseline flotation experiments were performed with coal using kerosene as collector and MIBC as frother. In this case, pH adjustments were carried out before the addition of frother and promoter. After 4 minutes of conditioning, the coal slurry was transferred to the column and flotation was carried out for 5 minutes. These experiments were performed for comparison with the floc flotation results.

RESULTS AND DISCUSSION

1. Sedimentation and Flocculation Experiments

In the last quarterly report, we had reported the effect of whole cells of *M. phlei* on the flocculation efficiency of IL No.6 coal. During this quarter, the effect of *M. phlei* on the flocculation of KY No.9 coal was investigated. Also, the flocculation characteristics of IL No.6 and KY No.9 coals in the presence of ruptured cells of *M. phlei* was studied as a function of pH, concentration and time.

The effect of ruptured cells on the amount of IL No.6 coal settled as a function of time is shown in Figure 1. As seen, with ruptured cells, the maximum amount coal settled is only about 60% after 3 minutes at a cell concentration of 300 ppm and pH of 6.5. The flocculating ability of ruptured cells of *M. phlei* is inferior when compared to the whole cells and this can be attributed to the loss of extracellular surfactants during sonication. The bacterial cell concentration and pH were selected from the contact angle measurements in the presence of ruptured cells. Figure 2 shows the effect of concentration on the flocculation efficiency for IL No.6 coal. It can be seen that in case of ruptured cells, the E_f increases as the concentration is increased and a maximum value of about 0.7 is reached only at concentrations above 300 ppm. Even though the extracellular surfactants have been removed during sonication, the bacterial cell wall may still contain some proteins and lipids

which can cause adherence to coal surface and hence flocculation. Because there might be very small amounts of proteins or lipids left in the cell wall, the concentration of ruptured cells (when compared with whole cells) required for flocculation is very high (> 300 ppm). The effect of pH on the flocculation efficiency of IL coal with ruptured cell is shown in Figure 3. In the absence of bacteria, the E_f is about 0.11 and does not change with pH. However, with ruptured cells, the E_f changes and is strongly dependent on pH. A clear maxima is observed in the neutral pH range which is close to the isoelectric point of the ruptured cells. However, as mentioned in the last report, the maximum E_f with whole cells is in the pH range of 3.5-4.5. At high ruptured cell concentrations of 300 ppm the maximum efficiency achieved is about 0.61 which is much lower compared to the results obtained with whole cells.

The effect of different flocculants on the flocculating behavior of KY No.9 coal was investigated. The amount of coal settled as a function of time is shown in Figure 4. With *M. phlei* whole cells, the maximum amount of coal settled is about 80% after 4 minutes. In the presence of conventional polymeric flocculants, the maximum amount settled is about 75-77%. However, with ruptured cells of *M. phlei* the maximum amount of KY coal settled was about 58%. The decrease in the amount of coal settled with ruptured cells is similar to IL coal and can be explained similarly. The effect of concentration of different flocculants on flocculation efficiency is shown in Figure 5. In the presence of whole cells, a maximum E_f of about 0.8 is obtained at concentrations greater than 200 ppm and remains constant at higher concentrations. On the other hand, with ruptured cells E_f increases with increasing concentration and a maximum E_f of 0.57 is observed at concentrations greater than 300 ppm. However, with PEO and PAM, E_f increases with increase in concentration but decreases at concentrations greater than 200 ppm which can be attributed due to stearic stabilization. This again demonstrates that the flocculation of coal with *M. phlei* is through hydrophobic interactions.

The effect of pH on the E_f of KY No.9 coal with whole cells is shown in Figure 6. The flocculation efficiency increases with increasing concentration and a maximum is observed at pH 4. This behavior is very similar to IL No.6 coal. However, the maximum E_f obtained was only about

0.78 while with IL No.6 coal the maximum obtained was 0.95. This difference might be due to the difference in surface hydrophobicities of both coals. IL No.6 coal is more hydrophobic compared to KY No.9 coal and this probably leads to higher flocculation efficiencies. At concentrations greater than 200 ppm, no further increase in E_f was observed. Similar tests were carried out with ruptured cells and the results are shown in Figure 7. A maximum E_f is observed in the slightly acidic to neutral pH range.

3. Floc Separation

After flocculation, the flocs were transferred to the column flotation cell. No pH adjustments were done and only MIBC as frother (0.7 kg/ton) was added. Nitrogen gas was used for flotation and an optimum flowrate of 0.6 L/min was maintained. Flotation was carried out for 5 minutes. For comparison purposes, the effect of kerosene and frother on the floatability of coal was evaluated at selected pH values. The flotation results for IL No.6 coal at pH 3.6 with different reagents is shown in Table 1 below.

Table 1. Flotation results of IL No.6 Coal at pH 3.6 (Gas flowrate 0.6 l/min and frother dosage 0.7 kg/ton)

	Combustible Recovery (%)	Pyritic Sulfur Rejection (%)	Ash Rejection (%)
Frother Only	50	45	44
Frother + Kerosene	76	56	46
Frother + Whole Cells	82	68	48
Frother + Ruptured Cells	60	50	45
Frother + PEO	28	35	40
Frother + PAM	25	33	42

With frother alone, the combustible recovery of coal is about 50% and the pyritic sulfur

rejection is 45%. In the presence of an oily promoter like kerosene, the combustible recovery and pyritic sulfur rejected increased substantially to 76% and 56% respectively. When coal flocculated with whole cells of *M. phlei* was floated, the amount of combustibles increased to 82% while the pyritic sulfur rejection increased to 68%. Adhesion of *M. phlei* increases the surface hydrophobicity of coal which probably enhances the floatability of coal. Although the combustible recovery increased by only 6% when compared with kerosene, the pyritic sulfur rejection increased by 12%. This meant that the flocculation of coal with *M. phlei* followed by flotation produced a higher quality product than flotation with kerosene alone. It should however be noted that pH and flotation time also can influence flotation of coal. The effect of pH and time on the floatability of coal are presently being evaluated.

When coal flocculated with ruptured cells of *M. phlei* was floated, only 60% of the combustibles were recovered along with a sulfur rejection of 50% which is due to the decreased hydrophobicity of *M. phlei* cells after sonication. However, when flotation was carried out after flocculation with synthetic flocculants such as PEO and PAM, the combustible recovery was only about 25-28% with a sulfur rejection of 33-35%. This is because of the hydrophilic nature of synthetic polymeric flocculants. Similar studies were conducted with KY No.9 coal which is less hydrophobic compared to IL No.6 coal and the results are shown in Table 2 below.

Table 2. Flotation results of KY No.9 coal at pH 3.9 (Gas flowrate 0.6 l/min and frother dosage 0.7 kg/ton)

	Combustible Recovery (%)	Pyritic Sulfur Rejection (%)	Ash Rejection (%)
Frother Only	45	38	42
Frother + Kerosene	60	50	44
Frother + Whole Cells	70	63	55
Frother + Ruptured Cells	48	40	40
Frother + PEO	20	30	35
Frother + PAM	18	31	38

As can be seen, the flotation results are very similar to those of IL No.6 coal in the presence of various flocculants and kerosene. The best results were obtained through flocculation followed by flotation with *M. phlei* whole cells. However, the combustible recovery is lower compared to that of IL No.6 coal. This might be due to KY No.9 coal being less hydrophobic compared to IL No.6 coal. These tests clearly indicate that *M. phlei* not only acts as an effective flocculant, but also acts as a good flotation collector for coal.

4. DLVO Calculations

In order to obtain a better picture of the interaction between coal/mineral and *M. phlei*, the interaction potential energy between these suspended particles was considered next. The theoretical analysis of the interactions between colloidal particles was originally developed by Derjaguin and Landau (1941) and Verwey and Overbeek (1946) in terms of repulsive and attractive potential energies of interaction (more commonly known as the DLVO theory).

The total interaction energy is calculated using the following equation :

$$V_T = V_R + V_A \quad (2)$$

where,

V_R = repulsive potential energy due to formation of electrical double layer around particles and

V_A = van der Waals attractive potential energy

The electrostatic repulsive force between mineral and *M. phlei* particles can be expressed by the following equation :

$$V_R = \frac{(\epsilon a_1 a_2)}{4 (a_1 + a_2)} (\psi_1^2 + \psi_2^2) \left[\frac{2 \psi_1 \psi_2}{(\psi_1^2 + \psi_2^2)} \ln \frac{(1 + \exp(-\kappa H_0))}{(1 - \exp(-\kappa H_0))} + \ln(1 - \exp(-2\kappa H_0)) \right] \quad (3)$$

where

ϵ is the dielectric constant of the aqueous medium = 8.84×10^{-10} ergs/mV².cm

a_1 is the diameter of coal/mineral particle = 10 μm - 15 μm

a_2 is the diameter of *M. phlei* = 1 μm

ψ_1 and ψ_2 are surface potentials of coal/mineral and *M. phlei* respectively

H_0 is the minimum separation distance between particle and *M. phlei* surface

Assuming $a_1 \gg a_2$, $a_1 a_2 / (a_1 + a_2)$ can be changed to a_2 and Equation 3 can be reduced to

$$V_R = \frac{\epsilon a_2}{4} (\psi_1^2 + \psi_2^2) \left[\frac{2 \psi_1 \psi_2}{(\psi_1^2 + \psi_2^2)} \ln \frac{(1 + \exp(-\kappa H_0))}{(1 - \exp(-\kappa H_0))} \right] + \ln(1 - \exp(-2\kappa H_0)) \quad (4)$$

The London - van der Waals attractive force V_A is given by :

$$V_A = - \frac{(a_1 a_2) A}{6 (a_1 + a_2) H_0} \quad (5)$$

Considering the diameter of coal/mineral particle to be much greater than that of *M. phlei*, Equation 5 is simplified to :

$$V_A = - \frac{a_2 A}{6 H_0} \quad (6)$$

The most important parameters determining the van der Waals interaction are the Hamaker constant (A), which is a material property, the distance (H_0) between the bacterium and coal/mineral, and the geometry of the particles.

The Hamaker constant, A_{312} , for coal/mineral-water-*M. phlei* system was evaluated using the following approximations.

$$A_{12} = [\sqrt{A_{11}} - \sqrt{A_{22}}]^2 \quad (7)$$

$$A_{13} = [\sqrt{A_{11}} - \sqrt{A_{33}}]^2 \quad (8)$$

$$A_{23} = [\sqrt{A_{22}} - \sqrt{A_{33}}]^2 \quad (9)$$

$$A_{312} = A_{32} + A_{11} - A_{31} - A_{21} \quad (10)$$

where 1 represents water, 2 represents *M. phlei* and 3 represents the mineral. The Hamaker constant for water (A_{11}) was selected from Viser (1972) as 4.38×10^{-13} ergs. The Hamaker constant for *M. phlei* has been estimated using the Fowkes equation (1967) as given below.

$$A_{22} = 6 \pi r_{11}^2 \gamma_s^d \quad (11)$$

where r_{11} represents the intermolecular distance and γ_s^d the dispersion component of surface free energy of a solid. According to Fowkes, for water and systems with volume elements such as oxide ions, metal atoms, CH_2 and CH groups which have nearly the same size, the value of $6\pi r_{11}^2 = 1.44 \times 10^{-14}$ can be used. The γ_s^d value for *M. phlei* has been estimated by Chen (1992) to be 43.6 dyne/cm. Using these values, the Hamaker constant for *M. phlei* was estimated to be about 6.26×10^{-13} ergs. The value for $6\pi r_{11}^2$ can be assumed to be valid even in the case of ruptured cells since the cell wall is made up of mainly lipids and proteins and contains CH_2 and CH groups. However, since the contact angle of ruptured cells was about 43° , the γ_s^d value was estimated to be 62.5 dyne/cm, and the Hamaker constant for ruptured cells was found to be 9×10^{-13} ergs.

The values of γ_s^d for coal and coal-pyrite were taken from Good et al. (1990) and Raichur (1992). It has been very well established that the value of γ_s^d for coal is independent of coal rank. Therefore, the same value has been used for both coal samples. The value for quartz was taken from

Fowkes (1967). Based on these values the following values of A_{33} were determined and are shown in Table 3.

Table 3. The γ_s^d values and Hamaker constants (A_{33}) for different minerals

Mineral	γ_s^d (dyne/cm)	A_{33} (ergs)
IL No.6 Coal	36	5.18×10^{-13}
KY No.9 Coal	36	5.18×10^{-13}
Coal pyrite	58.5	8.35×10^{-13}
Quartz	123	1.77×10^{-13}

For the above calculations, the separation distance, H_0 was varied from 1 to 100 Å and the various surface potentials at different pH values are listed below in Table 4.

Table 4. Zeta potential values of different samples (in mV) used for DLVO calculations

pH	Whole Cells	Ruptured Cells	IL No.6 Coal	KY No.9 Coal	ICPY	MPY	Quartz
2	-2	28	28	16	31	25	-6
3	-8	23	23	13	24	20	-20
4	-16	19	17	10	20	20	-26
6	-28	12	-4	-7	1	17	-33
8	-38	-13	-22	-21	-21	-6	-36
10	-46	-17	-34	-31	-28	-17	-39

Values of zeta potential were used in place of surface potentials for the total interaction energy calculations. The use of zeta potential in place of surface potentials is justified if it is considered that the plane of shear approximately coincides with the stern plane and that this layer is tightly bound

to, and may be considered a part of, the surface.

The value of k was calculated using the well known expression

$$\frac{1}{k} = \frac{4.3}{\sqrt{2 I}} \text{ \AA} \quad (12)$$

where I is the ionic strength of the solution. This equation is valid when water is used as solvent at 25°C. The ionic strength was calculated using the equation

$$I = \frac{1}{2} \sum [C_i Z_i^2] \quad (13)$$

where C_i is the concentration of ionic species and Z_i is the charge of the ionic species. In this case 0.01M NaNO₃ was used as electrolyte. Using this value, the value of I and then the value of k were calculated and found to be 0.1 and 0.03289/Å respectively.

The total interaction energy was calculated as a function of separation distance H_0 and as a function of pH. The separation distance was varied from 1 to 100 Å while the pH was varied from 2 to 10. The interaction energy for between mineral particles/whole cells and mineral particles/ruptured cells was calculated.

The total interaction energy for IL No.6 coal as a function of separation distance is shown in Figure 8. As can be seen with an increase in separation distance, the interaction energy becomes less negative and approaches zero at distances greater than 40 Å. Also, as the pH increases, the interaction energy becomes positive which means that repulsion becomes predominant. A similar behavior was observed with other minerals. Figure 9 shows the effect of pH on the total interaction energy for IL No.6 coal. As pH is increased, the total interaction energy becomes more negative up to pH 4. Above pH 4, the interaction energy becomes less negative. At pH 4, a minimum in interaction energy is observed and this corresponds to the maximum in adhesion and flocculation efficiency. Also, it is clear in Figure 9, that as H_0 increases the interaction energy increases thereby

decreasing adhesion.

Figure 10 compares the interaction energies of all the samples with whole cells of *M. phlei* as a function of pH. KY No.9 coal exhibited a similar trend as IL No.6 coal. However, coal-pyrite also had a minimum at pH 4 and the interaction energies were very similar to that of coal. This means that *M. phlei* should adhere to coal-pyrite as it does to coal which is, however, not the case. One of the reasons could be that the values of zeta potential of coal-pyrite measured may not be the true values. Since the surface of coal-pyrite is covered with coal/carbonaceous matter, the zeta potentials may be of the coal particles rather than of the pyrite particles. Also, the dielectric constant of water is used for calculations, but the dielectric constant of bound water is different for that of the bulk water and is dependent on the surface property of the mineral.

Further, the interaction energy calculations for the ruptured cell/mineral interface were also calculated. Figure 11. compares the interaction energies for whole cell/coal and ruptured cell/coal interface for IL No.6 coal. It is clear that upon rupturing the surface of bacterial cell becomes less hydrophobic and more positively charged. This leads to a substantial decrease in interaction energy when compared with whole cells which in turn decreases the amount of ruptured cells adhering to coal surface. Similar results were also observed with other minerals and are shown in Figures 12-14. These results demonstrate that due to increase in interaction energy, the adhesion of ruptured cells is less compared to whole cells. From the above discussion it is obvious that DLVO theory can explain the phenomena of bacterial adhesion onto coal and minerals with the exception of coal-pyrite.

FUTURE WORK

Currently, the effect of pH and time on the flotation of coal flocs is being investigated. The interaction between bacteria and coal surface is being studied by calorimetry. The effect of different parameters such as pH and concentration of *M. phlei* will be investigated.

REFERENCES

Chen, S., 1992, M. S. Thesis, University of Nevada, Reno.

Derjaguin, B. V. and Landau, L. D., 1941, "Theory of the Stability of Strongly Charged Lyophobic Sols, and of the Adhesion of Strongly Charged Particles in Solution of Electrolytes," *Acta Physicochim USSR*, Vol. 14, pp. 633-662.

Fowkes, F. M., 1964, "Attractive Forces at Interfaces," *Ind. Eng. Chem.*, Vol. 56, No. 12, pp. 40-52.

Good, R. J., Srivatsa, N. R., Islam, M., Huang, H. T. L. and Van Oss, C. J., 1990, "Theory of the acid-base hydrogen bonding interactions, contact angles, and the hysteresis of wetting: application to coal and graphite surfaces," *J. Adhesion Sci. Technology*, Vol. 4, No. 8, pp. 607-617.

Misra, M., Smith, R. W. and Raichur, A. M., *Novel Microorganism for Selective Separation of Coal from Ash and Pyrite*, Technical Progress Reports, DOE Grant No. DE-FG22-93PC93215.

Raichur, A. M., 1992, M. S. Thesis, University of Kentucky, Lexington, KY.

Verwey, E. J. W. and Overbeek, J. Th. G., 1946, "Long Distance Forces Acting Between Colloidal Particles," *Trans. Faraday Soc.*, 42B, pp. 117-123.

Viser, J., 1972, "On Hamaker Constants; a Comparison Between Hamaker Constants and Lifshitz-van der Waals Constants," *Adv. Colloid and Int. Sc.*, Vol.3, pp. 331-363.

Figure 1. Amount of coal settled as a function of time in the presence of different flocculants

Figure 2. The effect of concentration of different flocculants on the flocculation efficiency of IL No.6 coal

Figure 3. Flocculation efficiency of IL No.6 coal in the presence of ruptured cells as a function of pH

Figure 4. Amount of KY No.9 coal settled as a function of time in the presence of different flocculants

Figure 5. The effect of concentration of different flocculants on the flocculation efficiency of KY No.9 coal

Figure 6. Effect of pH on the flocculation efficiency of KY No.9 coal in the presence of whole cells of *M. phlei*

Figure 7. Effect of pH on the flocculation efficiency of KY No.9 coal in the presence of ruptured cells of *M. phlei*

Figure 8. The variation of total interaction energy as a function of separation distance at different pH values for IL No.6 coal and whole cells of *M. phlei*

Figure 9. Effect of pH on the total interaction energy for IL No.6 coal and whole cells of *M. phlei*

Figure 10. Comparison of total interaction energies for coal, coal-pyrite and quartz with whole cells of *M. phlei* as a function of pH

Figure 11. Comparison of interaction energies for whole cell/coal and ruptured cells/coal interface for IL No.6 coal

Figure 12. Comparison of interaction energies for whole cells/coal and ruptured cells/coal interface for KY No.9 coal

Figure 13. Comparison of interaction energies for whole cell/coal-pyrite and ruptured cells/coal-pyrite interface

Figure 14. Comparison of interaction energies for whole cells/quartz and ruptured cells/quartz interface