Refractive index and hygroscopic stability of $\text{Al}_x\text{Ga}_{1-x}\text{As}$ native oxides

D. C. Hall,^{a)} H. Wu, L. Kou, Y. Luo and R. J. Epstein

Department of Electrical Engineering, University of Notre Dame, Notre Dame, Indiana 46556

O. Blum and H. Hou

Sandia National Laboratory, Albuquerque, NM 87185

(Received xx May 1999; accepted for publication xx Month 1999)

We present prism coupling measurements on $\text{Al}_x\text{Ga}_{1-x}\text{As}$ native oxides showing the dependence of refractive index on composition ($0.3 \leq x \leq 0.97$), oxidation temperature ($400 \leq T \leq 500$), and carrier gas purity. Index values range from $n=1.490$ ($x=0.9$, 400°C) to 1.707 ($x=0.3$, 500°C). The oxides are shown to adsorb moisture, increasing their index by up to 0.10 (7%). Native oxides of $\text{Al}_x\text{Ga}_{1-x}\text{As}$ ($x \leq 0.5$) have index values up to 0.27 higher and are less hygroscopic when prepared with a small amount of O_2 in the $\text{N}_2+\text{H}_2\text{O}$ process gas. The higher index values are attributed to a greater degree of oxidation of the Ga in the film. © 1999 American Institute of Physics.

RECEIVED
JUL 21 1999
OSTI

Numerous advances in optoelectronics technology have occurred since the discovery of a wet thermal oxidation process for selectively converting Al-bearing III-V compound semiconductors to insulating, low index of refraction native oxides.¹ The low index has been employed for optical mode confinement in edge-emitting lasers² and vertical-cavity surface emitting lasers (VCSELs),³ high-contrast distributed Bragg reflectors (DBRs) for VCSELs,³⁻⁵ and to realize embedded microlenses.⁶ Other novel applications have included birefringent waveguides for phase matching⁷ and photonic lattices.⁸ The refractive index of $\text{Al}_x\text{Ga}_{1-x}\text{As}$ native oxides has been measured by single-wavelength ellipsometry ($x=0.8$, $n=1.63$ at 633 nm),⁹ angular Fabry-Pérot spectroscopic analysis ($x=1$, $n=1.52$ at ~ 870 nm),¹⁰ DBR reflectivity simulation ($x=1$, $n=1.55$ at ~ 1000 nm),⁵ variable-angle spectroscopic ellipsometry ($x=0.98$, $n=1.65$ at 240 nm to 1.56 at 1700 nm),¹¹ and spectroscopic ellipsometry ($x=1$, $n=1.77$ at 300 nm to 1.66 at 800 nm).¹² Disparities among reported values suggest the existence of material and process-dependent index variations. In this paper, we present results from prism coupling measurements on the refractive index of $0.6\text{--}1.4$ μm surface-oxidized $\text{Al}_x\text{Ga}_{1-x}\text{As}$ films with data on Al composition ($0.3 \leq x \leq 0.97$), oxidation temperature ($400^\circ\text{C} < T < 500^\circ\text{C}$), and carrier gas purity dependence. Index stability is monitored over time, revealing hygroscopic behavior.

The heterostructures used in this study were grown on semi-insulating GaAs substrates by Metal-Organic Chemical Vapor Deposition (MOCVD), and consist of 1 μm thick layers with Al compositions of $x=0.3$, 0.5 , 0.7 , 0.8 , and 0.9 , typically controlled to ± 0.005 . Two additional samples have 1.4 μm $\text{Al}_{0.4}\text{Ga}_{0.6}\text{As}$, or 0.6 μm $\text{Al}_{0.97}\text{Ga}_{0.03}\text{As}$, oxidation layers. All structures have 500 Å GaAs cap layers, and all layers are not intentionally doped. After removing the cap layer in a non-selective $1:8:80$ $\text{H}_2\text{SO}_4:\text{H}_2\text{O}_2:\text{H}_2\text{O}$ etch, conventional wet-thermal surface oxidation of the $\text{Al}_x\text{Ga}_{1-x}\text{As}$ layers is performed in a $2''$ quartz tube furnace with 0.66 l/min of N_2 bubbled through 95°C H_2O . Typical sample sizes are $\sim 4 \times 4$ mm^2 .

Oxidation in the reaction-rate limited (linear thickness growth) regime is confirmed for $x=0.8$ at 475°C and assumed for lower Al compositions and temperatures.

Prism coupling measurements of refractive index and thickness are performed with a Metricon¹³ Model 2010 instrument at $\lambda=632.8$ nm (TE mode). While limited to thicker films than can be characterized by ellipsometry, the technique requires no knowledge of substrate index or film absorption. Calibrated with a fused quartz standard ($n=1.45701$), the index accuracy is ± 0.0001 . Oxidation times are adjusted (from 20 min for $x=0.9$, 400°C to 696 min for $x=0.3$, 425°C) to obtain oxide thicknesses sufficient to support typically three optical modes ($d \sim 0.7$ μm). Care is taken to stop the oxidation front within the AlGaAs layer to obtain uniform index films. The consistency among mode angles for three mode films provides a measure of index homogeneity. The very low standard deviations (typically 0.0005) indicate highly uniform film composition vs. depth. This is confirmed for one $x=0.8$ oxide film by secondary ion mass spectrometry (SIMS) which shows flat Al, Ga, O, and As depth profiles (data not shown). Between 0.633 and 1.55 μm we measure an index decrease on $x=0.4$ films of just 0.020 , comparable to the dispersion measured elsewhere.^{11,12}

The dependence of the refractive index of oxidized $\text{Al}_x\text{Ga}_{1-x}\text{As}$ on the as-grown crystal's Al composition x is shown in Fig. 1 for oxidation temperatures of 400 , 425 , 450 , 475 and 500°C . Solid datum points represent films oxidized with a N_2 carrier gas purity of $> 99.999\%$ (~ 10 ppm O_2). The lines connecting data points are only to guide the eye. Each point consists of measurements on an average of 9 different samples oxidized in 2 or 3 separate oxidation runs. Open datum points correspond to oxidations on a few samples with a lesser N_2 purity ($\leq 99.95\%$, ≥ 300 ppm O_2), and reveal a significant index dependence on carrier gas. Except where shown otherwise, error bars for each datum point are smaller than the plotted symbols (as represented by the $\pm 1\sigma$ scale for the typical standard deviation of $\sigma=0.004$). In general, a decreasing oxide index is observed as lighter Al atoms replace Ga atoms in the material (i.e., as x increases), with exceptions for

^{a)}Electronic mail: dhall@nd.edu

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

FIG. 1. Dependence of the refractive index of oxidized $\text{Al}_x\text{Ga}_{1-x}\text{As}$ vs. Al composition, x , for different oxidation temperatures. Open symbols are for oxidations with ≥ 300 ppm O_2 in the N_2 carrier gas. For $x=0.97$, samples are oxidized both laterally (x) and from the surface ($+$).

$x \leq 0.4$ as discussed below. In Fig. 1, we also compare the index of $0.6 \mu\text{m}$ thick $\text{Al}_{0.97}\text{Ga}_{0.03}\text{As}$ films oxidized at $T=400\text{--}425^\circ\text{C}$ ($+$) from the surface ($n=1.498$) and (x) laterally ($n=1.521$, measured after removing the GaAs cap).

Figure 2 shows the dependence of the refractive index on oxidation temperature and carrier gas purity. For most compositions, $n(T)$ varies by <0.03 , although $\Delta n(T) \sim 0.16$ is observed for $x=0.3$ material as T increases from 450 to 500°C . This variation suggests a possible oxide phase transition. However, X-ray diffraction data on $x=0.3$ samples oxidized at 450 and 500°C do not reveal a structural difference, as both films are found to be completely amorphous. Data in Fig. 2 also show that the index of $\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}$ oxides formed with lower purity N_2 carrier gas is substantially higher ($\Delta n=0.06\text{--}0.27$) and less temperature dependent. We attribute this index increase to a more complete oxidation of the Ga in the films.

Oxidation reactions for AlGaAs vary substantially with Al composition and oxidizing environment. The wet thermal oxidation reaction converting AlAs to its native oxide becomes thermodynamically unfavorable ($\Delta G^{698} = +10 \text{ kJ/mol}$) when Al is replaced with Ga, accounting for the high Al selectivity in oxidation rate.¹⁴ However, in a dry O_2 environment, the oxidation rate of $\text{Al}_x\text{Ga}_{1-x}\text{As}$ has been shown to increase as the Al content decreases (for $x \leq 0.52$, $T \geq 550^\circ\text{C}$).¹⁵ Using a pure O_2 carrier gas bubbled through H_2O completely suppresses the oxidation of $\text{Al}_{0.98}\text{Ga}_{0.02}\text{As}$.¹⁴ However, the addition of only 0.1% (1000 ppm) O_2 to a N_2 carrier gas reduces the reaction activation energy and enhances (for $T \leq 490^\circ\text{C}$) oxidation rates of $\text{Al}_x\text{Ga}_{1-x}\text{As}$, significantly so for $x=0.6$ but very little for $x=0.77$.¹⁶ We also observe with lower purity N_2 that the oxidation rates for $x \leq 0.5$ increase and activation energies decrease.

The above results suggest that as x decreases, more O_2 is needed to fully oxidize the Ga in the $\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}$ alloy.

Fig. 2. Temperature dependence of the refractive index of oxidized $\text{Al}_x\text{Ga}_{1-x}\text{As}$ for different x values when oxidized in high purity N_2 (solid points) and with some O_2 in the N_2 carrier gas (open points).

With more O_2 available, more fully oxidized and thus denser, higher refractive index films are obtained. Data for $x=0.4$ and 0.5 films show a similar, but smaller, sensitivity to an increased O_2 content in the N_2 carrier gas as the Ga content in the films decreases. The index vs. composition data for $x \leq 0.5$ and lower purity N_2 in Fig. 1 are closer to expected values for $(\text{Al}_x\text{Ga}_{1-x})_2\text{O}_3$ based on reported indices for Ga_2O_3 films ranging from $n \sim 1.78$ ¹⁷ to 1.88 .¹⁸ The exact O_2 content in our lower purity N_2 was not controlled, and the full dependence of index on O_2 content requires further study. For the $x=0.4$ impure N_2 data in Fig. 2, the lower index values at 450 and 500°C correlate with lower oxidation rates, consistent with a drop in O_2 content for these runs. Although an O_2 content of 20% results in surface roughening,¹⁶ we observe smooth, specular surfaces with the lower O_2 levels which produce our higher index films.

Data on the refractive index variation with time following oxidation is summarized in Table I for several oxidized samples stored in ambient room temperature and relative humidity (RH) conditions. We have observed a consistent index drift of up to $+0.10$ (6.6%) over a time period of ~ 800 days. For consistency, all data in Figs. 1 & 2 were thus measured immediately after oxidation. We attribute this behavior to adsorption of moisture by a porous oxide, with a possible further chemical reaction of film constituents with the adsorbed moisture. Samples monitored for 15 days while stored in a dessicator at 0% RH showed 85-93% as much drift as those stored in ambient conditions (data not shown). This suggests the oxide film chemistry may evolve through reactions with existing moisture trapped either during wet oxidation or the initial measurement period.

The likelihood of additional moisture adsorption from the air is supported by the observation of accelerated index drift in the presence of 100% RH (Table II). By the end of 3 days, index drift saturates at levels comparable to those observed in Table I. Attempts to dry the samples of

Table I. Refractive index change during storage under ambient room temperature (295 K) and relative humidity (30-40%) conditions.

Starting material	Oxidation Temp. (°C)	Initial index	Time (days)	Final index	Index change
Al _{0.3} Ga _{0.7} As	450	1.483	804	1.559	+0.076
Al _{0.3} Ga _{0.7} As	500	1.651	802	1.712	+0.061
Al _{0.7} Ga _{0.3} As	400	1.531	9	1.549	+0.018
Al _{0.7} Ga _{0.3} As	400	1.535	888	1.618	+0.083
Al _{0.7} Ga _{0.3} As	425	1.535	3	1.544	+0.009
Al _{0.7} Ga _{0.3} As	425	1.533	8	1.544	+0.011
Al _{0.7} Ga _{0.3} As	425	1.540	55	1.558	+0.018
Al _{0.7} Ga _{0.3} As	425	1.535	823	1.604	+0.069
Al _{0.7} Ga _{0.3} As	500	1.547	791	1.613	+0.066
Al _{0.8} Ga _{0.2} As	425	1.517	819	1.616	+0.099
Al _{0.9} Ga _{0.1} As	400	1.465	10	1.488	+0.023

Table II. Refractive index change during exposure to 100% relative humidity (295 K).

Starting material	Oxidation Temp. (°C)	Initial index	Time (days)	Final index	Index change
Al _{0.3} Ga _{0.7} As	450	1.483	3	1.551	+0.068
Al _{0.3} Ga _{0.7} As	450	1.713	3	1.742	+0.029
Al _{0.3} Ga _{0.7} As	500	1.642	3	1.689	+0.047
Al _{0.8} Ga _{0.2} As	400	1.509	3	1.607	+0.098
Al _{0.9} Ga _{0.1} As	400	1.497	3	1.571	+0.074

Table II and reverse the index drift were largely unsuccessful. Progressively aggressive bakes culminating with 12 h at 160 °C decreased the index of the 4th sample just -0.017 to 1.590. While it is possible that a more effective drying technique is needed to remove adsorbed moisture, this data may indicate that a further chemical reaction has occurred, possibly involving residual As present in the films¹⁴ or unoxidized Ga.

We have also separately annealed 5 fully oxidized samples ($x=0.5$, 500°C, 2h) for 60-80 min in Ar at $T=400$ -800°C. Before annealing, their mean index increased during ~400 days in ambient air by 0.054 from 1.591 to 1.645. Upon annealing, the index decreases 0.044 (at 400 °C), 0.047 (500), 0.056 (600), 0.093 (700) and 0.100 (800). The large decrease above the sublimation temperature of As (613 °C) suggests the decrease may be due to the removal of residual As, although water desorption or a phase transformation may also be responsible.

Data in Table I for $x=0.7$ indicate that films oxidized at 400 °C are somewhat more hygroscopic than films oxidized at ≥ 425 °C. Index values at four different times for $x=0.7$, 425 °C oxides demonstrate a sublinear (saturating) increase. Higher composition films are also slightly more hygroscopic, possibly because these more rapidly oxidizing layers are more porous. The higher-index $x=0.3$ oxides obtained at 500 °C vs. 450 °C (high purity N₂) are denser and more stable. Data in Table II reveal that the densest film (a high index $x=0.3$ sample oxidized at 450 °C in lower purity N₂) has the smallest index drift (~43% of the low index, high purity N₂ sample), having essentially saturated at 0.028 in 1 day. It is unclear whether this increased index stability is due to less moisture adsorption by the denser, less porous film, or because the film begins more fully oxidized and thus undergoes minimal further chemical reactions with adsorbed moisture. For all samples, no oxide thickness variations are observed outside our $\pm 1\%$ measurement resolution. Fur-

ther material analysis is required to fully understand the nature of the changes observed.

In conclusion, we have characterized variations in the refractive index of wet oxidized AlGaAs with composition, oxidation temperature, and carrier gas purity. The index is found to vary up to 7% over time due to adsorbed moisture which may further react with the oxides. Denser, more stable native oxides of Al_xGa_{1-x}As ($x \leq 0.5$) are obtained when a small amount of O₂ is present in the carrier gas.

The authors gratefully acknowledge the support of J. H. Jackson of Metricon Corp. and NSF CAREER Award No. ECS-9502705.

- 1 J. M. Dallesasse, N. Holonyak, Jr., A. R. Sugg, T. A. Richard, and N. El-Zein, Appl. Phys. Lett. **57**, 2844 (1990).
- 2 M. R. Krames, E. I. Chen, and N. Holonyak, Jr., Appl. Phys. Lett. **65**, 3221 (1994).
- 3 D. G. Deppe, D. L. Huffaker, T. Oh, H. Deng, and Q. Deng, IEEE J. Selected Topics in Quantum Electron. **3**, 893 (1997).
- 4 M. J. Ries, T. A. Richard, S. A. Maranowski, N. Holonyak, Jr., and E. I. Chen, Appl. Phys. Lett. **65**, 740 (1994).
- 5 M. H. MacDougall, P. D. Dapkus, A. E. Bond, C.-K. Lin, and J. Geske, IEEE J. Selected Topics in Quantum Electron. **3**, 905 (1997).
- 6 O. Blum, K. L. Lear, H. Q. Hou, and M. E. Warren, Electron. Lett. **32**, 1406 (1996).
- 7 A. Fiore, S. Janz, L. Delobel, P. Van der Meer, P. Bravetti, V. Berger, E. Rosencher, and J. Nagle, Appl. Phys. Lett. **72**, 2942 (1998).
- 8 P. W. Evans, J. J. Wierer, and N. Holonyak, Jr., Appl. Phys. Lett. **70**, 1119 (1997).
- 9 A. R. Sugg, E. I. Chen, N. Holonyak, Jr., K. C. Hsieh, J. E. Baker, and N. Finnegan, J. Appl. Phys. **74**, 3880 (1993).
- 10 P. Heremans, M. Kuijck, R. Windisch, J. Vanderhaegen, H. D. Neve, R. Vounckx, and G. Borghs, J. Appl. Phys. **82**, 5265 (1997).
- 11 K. J. Knopp, R. P. Mirin, D. H. Christensen, K. A. Bertness, A. Roshko, and R. A. Synowicki, Appl. Phys. Lett. **73**, 3512 (1998).
- 12 A. Bek, A. Aydinli, J. G. Champlain, R. Naone, and N. Dagli, IEEE Photo. Technol. Lett. **11**, 436 (1999).
- 13 Metricon Corp., Pennington, NJ 08534.
- 14 K. D. Choquette, K. M. Geib, C. I. H. Ashby, R. D. Twisten, O. Blum, H. Q. Hou, D. M. Follstaedt, B. E. Hammons, D. Mathes, and R. Hull, IEEE J. Selected Topics in Quantum Electron. **3**, 916 (1997).
- 15 J. Shin, K. M. Geib, C. W. Wilmsen, P. Chu, and H. H. Wieder, J. Vac. Sci. Technol. A **9**, 1029 (1991).
- 16 R. S. Burton and T. E. Schlesinger, J. Appl. Phys. **76**, 5503 (1994).
- 17 P. A. Barnes and D. P. Schinke, Appl. Phys. Lett. **30**, 26 (1977).
- 18 M. Passlack, E. F. Schubert, W. S. Hobson, M. Hong, N. Moriya, S. N. G. Chu, K. Konstadinidis, J. P. Mannaerts, M. L. Schnoes, and G. J. Zydzik, J. Appl. Phys. **77**, 686 (1995).

Sandia is a multiprogram laboratory operated by Sandia Corporation, a Lockheed Martin Company, for the United States Department of Energy under Contract DE-AC04-04AL85000.