COAL AND COAL CONSTITUENT STUDIES
BY ADVANCED EMR TECHNIQUES

SEMI-ANNUAL TECHNICAL: 09/01/1996-03/01/1997

Authors:

R. Linn Belford
Robert B. Clarkson

Report Issue Date: 03/28/1997

DE-FG22-96PC96205--01

University of Illinois at Urbana-Champaign
Department of Chemistry
Box 18.6 CLSL - MC712
600 S. Mathews
Urbana, IL 61801

COAL AND COAL CONSTITUTENTS STUDIES BY ADVANCED EMR TECHNIQUES

by R. Linn Belford and Robert B Clarkson
University of Illinois at Urbana-Champaign

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

Advanced electronic magnetic resonance (EMR) methods are used to examine properties of coals, chars, and molecular species related to constituents of coal. During this grant period, progress was made on setting up a separate high frequency EMR system particularly appropriate for such studies and exploring the use of low-frequency dynamic nuclear polarization (DNP) to examine the interaction between fluids such as water and the surface of suspended char particles.

TABLE OF CONTENTS

Title page	1
Disclaimer	2
Abstract	2
Table of Contents	2
Executive Summary	3
Introduction	3
Results and Discussion	4
Conclusion	6
References	7
Figure	7

EXECUTIVE SUMMARY

W-band (100 Ghz) electronic magnetic resonance (EMR, EPR, or ESR) spectroscopy offers the extremely high resolution to discriminate among very similar chemical species that are constituents of coals and closely related materials such as chars and therefore to provide clues about chemical structures as well as an analytical tool. A W-band spectrometer exists in this laboratory, but as described in the proposal for this project, one of the first tasks was to set up another W-band station that would be particularly appropriate for study of such materials. This task has been progressing very well in the first six months of the project.

This report focuses on a new and exciting EMR technique - very low frequency pulsed dynamic nuclear polarization spectroscopy - for the study of the interfaces between coal-like particles and the water medium in which they are suspended. Here is described the discovery by this technique of a transient chemical interaction between certain char particles and the hydrogen atoms of water molecules in the bulk.

INTRODUCTION

The interactions of water in coal are important factors in all aspects of coal cleaning and utilization. It has long been suspected that water adsorbed in the pores of the coal matrix effects the EPR spectral line shapes seen by advanced Electron Magnetic Resonance (EMR) methods. Recently, we developed a very low-field pulsed dynamic nuclear polarization (DNP) spectrometer capable of observing the interactions of water with the surfaces of carbonaceous solids. In this report, we describe our first experiments making use of this novel DNP instrument, and outline some of the new insights which this approach can provide for coal research.

The first observation of solid-liquid electron spin density transfer by the contact Overhauser mechanism [1] seen in a system consisting of hardwood chars suspended in water is reported. Proton Dynamic Nuclear Polarization (DNP) enhancement was investigated in aqueous suspensions of several types of chars, where both positive and negative Overhauser effects were detected in different samples. The positive DNP effect is strong evidence for the presence of an electron-nuclear scalar interaction at solid-liquid interface.

To date, only a few studies have been published of solid-liquid energy transfer between sublevels in magnetic spin systems consisting of species with different gyromagnetic ratios [2-3]. All of these have described the dominant "solid-state" DNP effect due to pure dipole-dipole (through space) intermolecular interactions, such as those observed between free radical labels immobilized on a silica gel surface and solvent protons [2].

Contact DNP in solutions of paramagnetic ions is seldom observed for protons because of the very small contact hyperfine coupling that usually exists between unpaired electrons in a solute molecule and hydrogen atoms in solvent molecules. Until now, contact DNP for water protons was only observed in aqueous solutions of Mn^{2+} and Wurster's blue perchlorate [4,5]. The scalar coupling seen in aqueous hardwood char suspensions demonstrates for the first time

that there is electron delocalization from paramagnetic centers on the surface to water protons in the solvent, since the contact interaction demands that there be non-zero value for the electronic wave function at the nucleus. The positive DNP effect was accompanied by a significant difference between spin-lattice and spin-spin relaxation times of water protons.

The proton DNP enhancement observed in aqueous char suspensions was strongly temperature dependent. In contrast to ordinary free radical solutions, the increase of scalar polarization with temperature was observed. It suggests the possibility of exchange processes at the solid-liquid interface. For several hardwood chars the sign of the water proton DNP enhancement changed from negative to positive, indicating a change in the relative contributions from scalar and dipole-dipole nuclear-electron coupling.

RESULTS AND DISCUSSION

In the coupled nuclear-electron system, the time dependence of NMR polarization enhancement $\langle I_z \rangle$ can be described by the equation:

$$d\langle I_z \rangle / dt = -[\langle I_z \rangle - I_0 - \xi f(\langle S_z \rangle - S_0)] / T_{1n}, \quad (1)$$

where we used designations introduced by Abragam [6]. For many systems, it can be assumed that on the long time scale of nuclear relaxation, the electronic relaxation happens instantaneously. This assumption gives us the initial conditions for the integration of Eq.(1) in pulsed DNP conditions. For a two-pulse Hahn NMR sequence following after EPR saturating pulse, the master equation describing the relative enhancement A of the nuclear spin echo signal V derived from a polarized sample can be obtained from (1):

$$A = [V \exp(2\tau_1/T_{2n}) - V_0] / V_0 = A_{\max} Z [1 - \exp(-\tau_p/T_{1n})] \exp(-\tau_d/T_{1n}), \quad (2)$$

where V_0 is the amplitude of non-polarized echo, τ_p is the duration of the EPR saturation pulse, τ_1 is the time delay between 90° and 180° NMR pulses, $\tau_d = t - \tau_p$, $A_{\max} = -\xi f |\gamma_s/\gamma_I|$, and Z is the EPR saturation parameter.

¹H pulsed DNP relaxation technique at low magnetic field has been applied [7]. A spiral delay line (helix) was used to enhance the EPR saturating field. The duty cycle of the EPR saturating pulses can be chosen to avoid microwave heating of the sample. Experiments were carried out under the following conditions: $\nu_1 = \omega/2\pi = 0.5\text{MHz}$, $B_0 = 117.5\text{G}$; the electron resonance frequency $\nu_s = 328.9\text{MHz}$.

Samples

Samples of chars were obtained from various kinds of woods (e.g. hardwoods, softwoods) by charring under H_2 and CH_4 flow. The samples were heated at the rate of 10° C per hour according to a pre-selected heat treatment profile, with a maximum temperature ranging from 420-720°C. Prior to measuring, chars were finely ground to a particle size of about 10 μm . The samples were suspended in water, and then bubbled with pure helium for 15 min. The EPR spectra of chars in water consisted of a single Lorentzian line with a peak-to-peak line width of about 0.5 G, and a typical free

radical g-factor, close to the free electron value of 2.0023. Experimental details of char synthesis are described in [8].

Correlation of experimental and theoretical results has been achieved in this work through consideration of proton-electron spin dipole-dipole interaction and of chemical exchange of solvent molecules. The Table lists the key parameters measured for several different carbon chars.

Table. DNP/NMR data at magnetic field 117G and molecular-kinetic parameters in aqueous suspensions of chars.

No	Material (atmosphere of charring)	T_{1n}, s (300° K)	T_{2n}, s (300° K)	$\Delta T_n^{-1},$ s^{-1}	f	A_{max} (360° K)	M	$E_n,$ kcal/mol e
1	Hardwood (CH ₄)	0.58 ±0.03	0.08 ±0.004	10.78 ±0.05	0.75 ±0.04	+44 ±2.0	14.69 ±0.02	13.44 ±0.02
2	Hardwood (H ₂)	0.47 ±0.03	0.09 ±0.004	8.98 ±0.05	0.8 ±0.04	+20 ±1.0	11.99 ±0.02	13.48 ±0.03
3	Softwood (H ₂)	0.43 ±0.02	0.11 ±0.005	6.77 ±0.03	0.81 ±0.04	-28 ±1.5	9.41 ±0.03	14.12 ±0.03
4	Starch (H ₂)	0.14 ±0.006	0.095 ±0.005	3.38 ±0.02	0.94 ±0.05	-32 ±1.6	4.7 ±0.02	14.21 ±0.03
5	Fructose (H ₂)	0.17 ±0.008	0.120 ±0.006	2.45 ±0.01	0.93 ±0.05	-46 ±2.3	3.5 ±0.01	14.28 ±0.03

The Figure at the end of this report illustrates the proton NMR signals seen in the experiment, both with and without DNP enhancement. A model of molecular migration at the solid-liquid interface was constructed to account for the experimental DNP observations. According to the model, expression (2) can be represented in the form:

$$A = -|\gamma_s/\gamma_H| f Z (1 - \delta) / 2(1 + \delta), \quad (3)$$

where we introduced a designation:

$$\delta = M(\tau_e/\tau_i)/(1 + \omega_s^2\tau_e^2) = (1 - 2\xi)/(1 + 2\xi) \quad (4)$$

and parameter M can be defined as the relative intensity of the scalar and d-d interactions. Assuming an Arrhenius temperature dependence for the correlation times in (4), the value of the activation enthalpy of the chemical exchange process (water desorption) at the solid-liquid interface is found to be $E_n = 13.5$ kcal/mole. A value of activation energy $E_t = 2.1$ kcal/mole for translational diffusion and for electronic relaxation $E_s = 2.0$ kcal/mole also were obtained by the fitting program. Calculations also give the value of the exchange correlation time $\tau_e(300^\circ\text{K}) = 1.6 \times 10^{-6}$ s. Utilizing the difference between the experimental proton T_{1n} and T_{2n} relaxation times and DNP results, it is possible to estimate the contact hyperfine coupling constant at the solid-liquid interface $a = 5.3 \times 10^{-3}$ MHz. The values of the enthalpy of activation of chemical exchange E_n , as well as the hyperfine scalar constant a strongly suggest the presence of weak chemisorption bonds at the solid/liquid interface that are capable of facilitating the electronic delocalization whose effect is observed in these DNP

experiments.

CONCLUSIONS

The temperature dependence of the DNP effect seen in aqueous char suspensions is the result of a delicate balance between dipole-dipole and scalar interactions as well as the competition between corresponding correlation times at the solid/liquid interface. The translational diffusion of water molecules is responsible for d-d relaxation, which dominates at low temperatures. The scalar interaction is modulated mainly by electron spin relaxation and an isotropic proton-electron spin chemical exchange process on the surface. The scalar relaxation of Type II [6] is responsible for solid-liquid interactions in chars suspensions at room temperature. As the temperature increases, the effect of exchange interactions in char suspensions becomes predominant because $E_h > E_s$, and the positive dynamic polarization increases. The increase in the relative contribution of the contact interaction to proton relaxation mainly is a result of the decrease in the life time τ_h ($E_h > E_s$) of the water protons in the short-lived hydrated complex at the hardwood chars interface as the temperature increases. The possible influence of a gradual transition from the pure Overhauser effect to the pure "solid-state" effect on the value of DNP enhancement can not be in principle excluded in such systems. In any case at the paramagnetic surface of hardwood char, the water protons are subjected to a strong scalar coupling with the unpaired electron, but at low temperatures the exchange process is far too slow to modulate the scalar coupling fast enough to stimulate the relaxation transitions required to produce a positive DNP enhancement. Since the main rate constant for the build-up of the Overhauser effect is the nuclear spin-lattice relaxation time T_{1n} , positive polarization will occur only if the lifetime τ_h of the solvent water protons at the hardwood char interface is comparable to T_{1n} on the surface. The value of τ_h obtained here exceeds the value for electron relaxation τ_s on the surface of chars under study, and electron-nuclear cross-relaxation process thus can occur during the proton-electron contact. When a water molecule jumps from the surface, the positive polarization on the hydrogen atoms will be retained, but will start to decay to the negative value expected for dipolar coupling with the relaxation time of protons in the diamagnetic molecule. If, however, the water molecule makes contact with the paramagnetic surface again before negative polarization is established, the average polarization of water protons will remain positive.

It should be noted, that the basic condition for EPR hyperfine structure observation in such systems

$$a \tau_e > 1$$

is not satisfied in the case of aqueous chars suspensions. As a result, no superhyperfine structure in the EPR spectrum has ever been observed in such systems. The proton NMR chemical shifts for molecules adsorbed on paramagnetic catalytic surfaces also have in general been obscured by broad resonance lines.

REFERENCES

1. Overhauser, A., *Phys. Rev.* 1953, 91, 476.
2. Gitti, R., Wild, C., Tsiao, C., Zimmer, K., Glass T.E. and Dorn, H.C., *J.Am.Chem.Soc.*, 1988, 110, 2294.
3. Wind, R.A., Duijveshijn, M.J., Van Der Lagt, C., Manenshijn, A. and Vriend, J., *Prog. NMR Spectrosc.* 1985 17, 33.
4. Codrington, R. and Bloembergen, N., *J.Chem.Phys.*, 1958, 29, 600.
5. Collingwood, J. and White, J., *Mol.Phys.*, 1973, 25, 1241
6. Abragam, A., in: *Nuclear Magnetism*, Oxford Univ. Press, Oxford, 1961.
7. Odintsov, B.M., Belford, R.L. and R.B. Clarkson, *J. Phys. Chem.*, 1997, 101, 116.
8. Boyer, S., Clarkson R.B., *Colloids Surf.*, A. 1994, 82, 217.

FIGURE

a) Proton NMR echo signal in softwood char aqueous suspensions at $B_0=117$ G without EPR pumping ($B_{IS}=0$, $\tau_1=8$ ms);
b) **A** - the same NMR echo signal with 10-fold decrease in NMR receiving channel sensitivity; **B** - negative proton echo signal polarization in softwood char aqueous suspensions as a result of d-d solid-liquid interactions ($B_{IS}=0.5$ G, $\tau_1=8$ ms, $\tau_p=200$ ms, $\tau_d=0$). c) Positive proton echo signal polarization in hardwood char suspended in water as a result of scalar intermolecular interactions: **A** - $B_{IS}=0$; **B** - $B_{IS}=0.2$ G, $\tau_1=4$ ms, $\tau_p=200$ ms, $\tau_d=0$.