DE/PC91311--715

QUARTERLY PROGRESS REPORT

ON

CONFIGURATIONAL DIFFUSION OF ASPHALTENES IN FRESH AND AGED CATALYST EXTRUDATES

Grant No. DE-FG22-91PC91311

3-20-95 to 6-20-95

James A. Guin

Chemical Engineering Department
Auburn University
Auburn, AL 36849

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

RECEIVED
USDOE/PETC
95 JUN 26 AM 10:49
ACQUISITION & ASSISTANCE DIV

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Table of Contents

Objective and Work Statement	1
Summary of Progress	3
Planned Work	4
Detailed Progress-----Hindered Adsorption-Diffusion of Asphaltenes	
Experimental	4
Materials	4
Apparatus and Procedures	4
Hindered Adsorption-Diffusion Model for Asphaltenes	5
Results and Discussions	7
Calibration of SECC Columns	7
Estimation of Properties of Polystyrene Solution	8
Simulation of Asphaltene Diffusion into Porous Catalyst	11
References	13

Statement of Work

Configurational Diffusion of Asphaltenes in Fresh and Aged Porous Catalyst Extrudates

Objective: The objective of this research is to determine the relationship between the size and shape of coal and petroleum macromolecules and their diffusion rates i.e., effective diffusivities, in catalyst pore structures. That is, how do the effective intrapore diffusivities depend on molecule configuration and pore geometry.

Task 1. Relationship Between Effective Intrapore Diffusion Coefficients, Molecular Size and Pore Geometry.

Finite bath-type diffusion experiments will be performed using both coal and petroleum-derived macromolecular species, e.g. asphaltenes, as well as model compounds, e.g. porphyrins, polymers, of known molecular size. By monitoring the concentration of solute macromolecules in the bath, the effective intrapore diffusion coefficients will be determined through application of the appropriate diffusion equations. Macromolecular species concentrations will be monitored by size exclusion chromatography (SEC). Relationships will be sought between the size, and shape, e.g. planar, coil, of the diffusing solutes and the pore geometry (pore size distribution) of the catalyst support. The effects of molecule configuration and catalyst pore size distribution on the effective intrapore diffusivity will be examined. Specially prepared laboratory catalysts with very narrow pore size distributions and other model porous media, e.g. porous Vycor glass, will be utilized in the experiments. Pore structures of all catalysts and other porous media will be characterized by mercury porosimetry and surface area (BET) analysis.

Task 2. Effects of Solvent Composition, Solute Concentration, and Temperature on the Molecular Configuration and Diffusion Rate of Coal and Petroleum Asphaltenes in Catalyst Pores.

Diffusion experiments such as in Task 1 will be performed with varying solvent compositions, i.e., paraffinic-aromatic mixtures, to examine the effects of the state of molecular aggregation (self-assemblies) on the rates of diffusion of coal and petroleum asphaltenes in the catalyst pores. Similar experiments will be performed to study the effect of *temperature* and solute (macromolecule) *concentration* on the state of molecular configuration and aggregation on the resulting pore diffusivity.

Task 3. Assessment of Diffusional Limitations in Aged Catalysts

Diffusivity measurements such as conducted in Task 1 will be performed with both model compound and coal-derived macromolecular species using extrudate-type aged catalysts from laboratory experiments as well as aged catalysts obtained from actual coal liquefaction pilot plants such as the Wilsonville, AL Advanced Coal Liquefaction R & D Facility. From the experimental diffusivities so obtained, an evaluation of effects of changes in catalyst pore structure, e.g. tortuosity, pore plugging, shall be made. The changes in pore diffusivities associated with the pore structural changes caused by coke and metals deposition will be investigated, as compared with the fresh catalysts. As assessment of the relationship of increased diffusional limitations to coke and metals deposition in the catalyst pores will be made based on the results of the diffusivity measurements. The degree to which pore diffusivities can be restored to their original values by carefully controlled oxidation and/or extractive catalyst regeneration techniques also will be explored. The practical importance of these findings to coal liquefaction technology will be evaluated.

Summary

This quarter, adsorptive diffusion of petroleum asphaltenes in THF into porous catalysts were performed. A simplified mathematical model for asphaltene diffusion was developed. The molecular weight distribution of asphaltenes was ascertained on SEC using polystyrene standards. Several asphaltene fractions were defined according to their equivalent molecular weights of polystyrene standards. The properties of polystyrenes in THF were estimated using appropriate equations. The asphaltene diffusion data were simulated fairly well by the simplified mathematical model, and some of the diffusional parameter values were obtained by the simulation.

Planned Work

Next quarter, adsorptive diffusion experiments of several different petroleum asphaltenes into porous catalysts will be performed. Asphaltenes from coal liquid residua will also be employed as solutes in the study. The adsorption-diffusion parameters of asphaltenes will be ascertained by simulating experimental data with the simplified mathematical model. The adsorption-diffusion behavior of different asphaltenes will be compared.

Hindered Adsorption-Diffusion of Asphaltenes

EXPERIMENTAL

1. Materials

Chemicals. The asphaltenes used in the adsorption-diffusion experiments were extracted from a petroleum asphalt, AAD-1. The detailed extraction procedure was described in the last quarterly report. HPLC grade tetrahydrofuran (THF) was used as solvent in the diffusion experiments. Polystyrenes with narrow molecular weight distribution were used as calibration standards for analysis of asphaltenes on SEC.

Catalyst. A commercial unimodel catalyst, Criterion 324, with an average pore diameter of 125 Å, was used in this study. Some typical catalyst parameters are shown in Table 1. The catalyst extrudates were crushed to -60+80 mesh size (-250+180 µm). Catalyst samples were calcined at 673 K for 12 hours prior to use in diffusion experiments.

2. Apparatus and Procedures

Diffusion Experiments. Diffusion experiments were performed using the adsorptive uptake of asphaltenes in THF from a finite bath surrounding the catalyst pellets. Experiments were conducted in a glass bottle placed in a shaker at a constant temperature of 30 °C. The diffusion process was monitored periodically by analyzing the concentration of asphaltenes in the bath solution using SEC.

SEC Equipment. An SEC (size exclusion chromatograph) device with a UV detector was used to analyze the concentration of asphaltenes in THF. Four columns, with nominal pore sizes of 1000, 1000, 500 and 500 Å, were placed in series. HPLC grade THF was used as

mobile phase with a flow rate of 1 cc/min. Before use in SEC analysis, THF was filtered through a filter paper with 0.1 μm nominal pore size and was degassed for ten minutes by using a sonicator. The THF reservoir was purged with He gas to keep THF from forming peroxides. Each asphaltene sample for SEC analysis was filtered before injection through a 0.1 μm syringe filter.

HINDERED ADSORPTION-DIFFUSION MODEL FOR ASPHALTENES

Due to the complexity, the asphaltenes are grouped into several fractions according to their molecular weights, which were ascertained from SEC analysis. Besides the assumptions described before, it is also assumed that during adsorption-diffusion process, the properties of each fraction, such as the molecular size, the diffusivity, and the adsorption capacity, are independent of every other fraction. For each fraction j , the following mass balance equations hold:

$$\frac{\partial(K_{pj}eC_j)}{\partial t} + \frac{\partial(\rho_p q_j)}{\partial t} = \frac{1}{r^2} \frac{\partial}{\partial r} (r^2 D_{ej} \frac{\partial C_j}{\partial r}) \quad (1)$$

$$C_j|_{t=0} = 0 \quad (2)$$

$$\frac{\partial C_j}{\partial r} \Big|_{r=0} = 0, \quad C_j|_{r=R} = C_{bj}(t) \quad (3)$$

$$\frac{d(V_b C_{bj})}{dt} = -4\pi R^2 k D_{ej} \left(\frac{\partial C_j}{\partial r} \right) \Big|_{r=R} \quad (4)$$

$$C_{bj}|_{t=0} = C_{bj0} \quad (5)$$

In the above equations, q_j is the equilibrium adsorption for fraction j . It is assumed that the amount of equilibrium adsorption for each fraction is linearly dependent on its concentration C_j or

$$q_j = K_j C_j \quad (6)$$

With the above assumptions, the adsorption-diffusion mathematical model can be solved analytically, and the solution for dimensionless bath concentration of each fraction is

$$\theta_{bj} = \frac{B_j}{1+B_j} + 6B_j \sum_{k=1}^{\infty} \frac{\exp(-b_k^2 t_j^*)}{B_j^2 b_k^2 + 9(1+B_j)} \quad (7)$$

where, the b_k 's are the non-zero roots of

$$\tan(b_k) = \frac{3b_k}{3+B_j b_k^2} \quad (8)$$

and

$$\theta_{bj} = \frac{C_{bj}}{C_{b0j}} \quad (9)$$

$$B_j = \frac{V_b}{V_p} \frac{1}{K_{pj}e + \rho_p K_j} \quad (10)$$

$$t_j^* = \frac{D_{ej}}{R^2} \frac{1}{K_{pj}e + \rho_p K_j} \quad t = \frac{D_{ej}}{R^2} \frac{V_p}{V_b} B_j t \quad (11)$$

Since for a typical adsorptive diffusion experiment, the values for most parameters

are known except those for B_j and D_{ej} . Thus, equation (7) can be rewritten as

$$\theta_{bj} = f(B_j, D_{ej}, t) \quad (12)$$

RESULTS AND DISCUSSION

1. Calibration of SEC Columns

SEC analysis of asphaltenes requires the use of calibration standards to determine the average molecular weights of the fractions from elution volumes. Studies have shown that a linear calibration curve obtained from polystyrene standards gives reasonable approximate values of the molecular weights of asphaltene fractions. Thus a calibration curve was first obtained by the use of some polystyrenes with narrow molecular weight distribution as calibration standards.

Polystyrene standards with weight average molecular weights ranging from 500 to $5 \cdot 10^4$ were first dissolved in THF, each with concentration of 1 mg/cc. The solution of polystyrene/THF was analyzed via SEC. The logarithm of polystyrene molecular weight vs. elution volume is plotted in Figure 1. It can be seen that a good linear fit of $\log(M_w)$ vs. elution volume is obtained as:

$$\log(M_w) = -0.152 V_R + 8.015 \quad (13)$$

Figure 2 shows an SEC chromatogram for a solution of asphaltenes in THF (0.05 mg/cc). There are two x-axes in this figure, one is the elution volume, the other is the equivalent polystyrene molecular weight calculated from equation (13). In the simulation of

experimental asphaltene diffusion data, ten fractions of the asphaltenes will be defined in terms of the equivalent eluted polystyrene molecular weights. No attempt was made to determine the actual molecular weights of the various asphaltene fractions.

2. Estimation of Properties of Polystyrene Solution

As discussed above, for simulation of the diffusion uptake process, several asphaltene fractions will be defined in terms of polystyrene standards. To do the simulation, certain properties of polystyrenes in THF are needed, such as viscosity of THF, molecular sizes and diffusivities of polystyrenes in THF. These properties of polystyrene solution will be estimated in the following section.

a. Solvent Viscosity

The viscosity of THF can be calculated from the following empirical equation, as shown by Reid, et al.⁽¹⁾

$$\log (\eta_0) = A \left(\frac{1}{T} - \frac{1}{T_0} \right) \quad (14)$$

where, η_0 —the viscosity of solvent, centipoise,

T—temperature, K.

For THF, A is 419.79 and T_0 is 244.46. Thus, the viscosity of THF at 30 °C is 0.466 cp, or 4.66×10^{-3} g/cm-s.

b. Polystyrene molecular size in THF

The polymer molecular size in a solvent can be estimated from the intrinsic viscosity of the solution. If the polymer molecules in solution are considered to be a very dilute

suspension of rigid spheres, the suspension viscosity η can be described by the following Einstein equation⁽²⁾.

$$\eta = \eta_0 (1 + 2.5\phi) \quad (15)$$

where, η_0 —viscosity of pure solute, g/cm-s

η —viscosity of solution, g/cm-s

ϕ —volume fraction of solute in solution, cm³ solute/cm³ solution

and

$$\phi = \frac{N_0 CV}{M_w} \quad (16)$$

where, N_0 —Avogadro number, 6.023×10^{23} molecules/mol

C —concentration, g solute/cm³ solution

V —volume of 1 solute molecule, cm³

M_w —solute molecular weight, g/mol

and

$$V = \frac{4}{3} \pi r_A^3 \quad (17)$$

Actually, equation (15) is only the first term of a series

$$\eta = \eta_0 (1 + a\phi + b\phi^2 + \dots) \quad (18)$$

Combining the above equations, we have

$$\eta = \eta_0 \left(1 + \frac{10}{3} \frac{\pi N_0 r_A^3}{M_w} C + O(C^2) \right) \quad (19)$$

or

$$\frac{\eta}{\eta_0} - 1 = \frac{10}{3} \frac{\pi N_0 r_A^3}{M_w} C + O(C^2) \quad (20)$$

Dividing the above equation by c on both sides and taking limit as c approaches zero

$$\eta^i = \lim_{c \rightarrow 0} \left(\frac{1}{C} \left(\frac{\eta}{\eta_0} - 1 \right) \right) = \frac{10}{3} \frac{\pi N_0 r_A^3}{M_w} \quad (21)$$

where, η^i is called intrinsic viscosity, with units of $\text{cm}^3 \text{ solution/g-solute}$

Thus, the radius of a spherical molecule in a dilute solution can be calculated by

$$r_A = \left(\frac{3}{10\pi N_0} \right)^{\frac{1}{3}} (\eta^i M_w)^{\frac{1}{3}} = 5.413 \times 10^{-9} (\eta^i M_w)^{\frac{1}{3}} \quad (22)$$

According to the well known Mark-Houwink relation, the relationship between the viscosity average molecular weight of a polymer M_v and the intrinsic viscosity η^i is

$$\eta^i = K M_v^{0.5} \alpha^3 \quad (23)$$

For polystyrene standards with narrow molecular weight distribution, the weight average molecular weight M_w can be used instead of the viscosity average molecular weight M_v . The value of α ranges from 1 for theta solvents to about 3 and K is a constant depending on the solvent used. For polystyrene in THF, the theta temperature is $29^\circ\text{C}^{(3)}$, which is very close to our experimental temperature (30°C), and K value is $82 \pm 5^{(3)}$. Thus, the equivalent spherical radius of polystyrene in THF will be

$$r_A = 2.35 \times 10^{-9} M_w^{0.5} \text{ (cm)} \quad (24)$$

c. Molecular Diffusivity of Polystyrene in THF

Many liquid diffusion coefficients can be calculated from the well known Stokes-Einstein equation, which predict, for diffusion of a large spherical molecule A through a dilute solvent B

$$D_{AB} = \frac{kT}{6\pi\eta_0 r_A} \quad (25)$$

where, k is the Boltzmann's constant, with the value of 1.38×10^{-16} erg/molecule-K.

3. Simulation of Asphaltene Diffusion into Porous Catalyst

As shown in equation (12), in order to simulate the adsorption-diffusion behavior of asphaltenes into catalyst pores, the adsorption parameter B_j (or equilibrium adsorption constant K_j in equation (6)) for each fraction is needed. Because of the stability of asphaltenes in THF, it is difficult to get an equilibrium constant due to the relatively long time interval required for equilibrium to be reached. This problem can be overcome by the following data treatment method.

As shown by equation (12), for diffusion experimental data of an asphaltene fraction, namely the bath concentration and the diffusion time, the only unknown value will be the adsorption parameter B_j if the value of the effective diffusivity is known. In this study, it is assumed that the effective diffusivity of an asphaltene fraction is equal to that of polystyrene with same elution volume on SEC. Thus, by simulating the experimental diffusion data with the mathematical model, the adsorption-diffusion parameters can be ascertained.

Table 2 gives the parameter values for polystyrenes in THF. Figure 3 shows SEC

analysis of asphaltene bath solution sampled at different time intervals during a diffusion experiment. It can be seen that the equivalent molecular weights of the petroleum asphaltenes are in the range of 100 to 50000. For most molecular weights or elution volumes, the bath concentration decreases as diffusion time increases. For some asphaltene fractions, however, particularly when elution volume is less than 26.5 (equivalent molecular weight larger than 9705), the concentration lines cross with respect to diffusion time. This unusual behavior may result from phenomena such as the agglomeration of smaller molecules to larger ones, a process which needs further investigation.

Figure 4 shows simulation of experimental diffusion data compared with the model solution. It can be observed that for most molecular weight regions, the model fits experimental data fairly well. By simulating the experimental data with the mathematical model for each asphaltene fraction, the linear adsorption constant K_j can be ascertained, which is shown in Figure 5. It can be seen that as the equivalent molecular weight of an asphaltene fraction increased, the adsorption constant increased.

Table 1. Parameter Values of Criterion 324 Catalyst

weight W (g)	density ρ_p (g/cm ³)	particle size R (cm)	pore diameter d (cm)	tortuosity τ	porosity ϵ (cc/cc)
0.2	1.4	0.021	$1.25 \cdot 10^{-6}$	4.5	0.66

Table 2. Estimated Parameter Values for Polystyrenes in THF

fraction number	elution volume, V_t cc	molecular weight, M_w g/mol	molecular size, r_A $\cdot 10^8$ cm	molecular diffusivity, D_{AB} $\cdot 10^6$ cm ² /s	effective diffusivity, D_e $\cdot 10^6$ cm ² /s
1	22.5	39355	46.6	1.02	0.00076
2	24.2	21962	34.8	1.37	0.0054
3	25.8	12256	26.0	1.83	0.024
4	27.5	6839	19.4	2.45	0.069
5	29.2	3817	14.5	3.28	0.15
6	30.8	2130	10.8	4.39	0.28
7	32.5	1189	8.10	5.88	0.48
8	34.2	663	6.05	7.87	0.75
9	35.8	370	4.52	10.5	1.13
10	37.5	207	3.38	14.1	1.64

References

1. R. C. Reid, et al., The Properties of Gases and Liquids, 3rd ed., McGraw-Hill Inc., 1977.
2. A. Rudin, and H. K. Johnson, Polymer Letters, 9, 55(1971).
3. J. Brandrup and E. H. Immergut, Polymer Handbook, John Wiley & Sons, 1966.

Figure 1. Calibration Curve of SEC by Polystyrene Standards

Figure 2. SEC Chromatogram of Petroleum Asphaltene

Figure 3. Adsorptive Diffusion Uptake of Asphaltenes in THF into Criterion 324 Catalyst at 30°C. ($C_0=0.05$ mg/ml)

Figure 4. Model Simulation of Uptake of Petroleum Asphaltenes into Criterion 324 Catalyst at 30 °C
Solid lines: model prediction
Symbols: experimental data

Figure 5. Relationship between Equivalent Asphaltene Molecular Weight and Adsorption Constant K